WESTINGHOUSE
ELECTRIC CORPORATION

MASTER

BETTIS PLANT
BETTIS SITE
P.O. BOX 1468
PITTSBURGH 30, PA.

NOV 20 1957

Manager, Pittsburgh Area Office
U. S. Atomic Energy Commission
P. O. Box 1105
Pittsburgh 30, Pennsylvania

NOTE

This document is an interim memorandum prepared primarily for internal reference and does not represent a final expression of the opinion of Westinghouse. When this memorandum is distributed externally, it is with the express understanding that Westinghouse makes no representation as to completeness, accuracy, or usability of information contained therein.

Dear Sir:

At the October 24 and 25 meeting between USAEC, AECL, and Bettis personnel, the theoretical aspects of the effect of radiation upon the $\gamma \rightarrow \alpha + \gamma_2$ transformation in uranium-niobium alloys were discussed. The theoretical model discussed involving the annihilation of nuclei of the new phase by the action of displacement spikes is given in the enclosed document, which is submitted for transmittal to Dr. E. C. W. Perryman, Head, Research Metallurgy, AECL, at his request.

Very truly yours,

D. M. Wroughton
Irradiation Coordinator
Bettis Plant

DEThomas/dat
Attachment: WAPD-IPC-743
Distribution List XXI, Col. (1) and (3)

D. E. Thomas, ALW, 10 copies

Transmitted by:

NOTE

This document is an interim memorandum prepared primarily for internal reference and does not represent a final expression of the opinion of Westinghouse. When this memorandum is distributed externally, it is with the express understanding that Westinghouse makes no representation as to completeness, accuracy, or usability of information contained therein.

483 - 001

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency Thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

DISCLAIMER

Portions of this document may be illegible in electronic image products. Images are produced from the best available original document.

ANNIHILATION OF NUCLEI BY DISPLACEMENT SPIKES

D. E. Thomas

Consider any point in a gamma-phase alloy matrix. Allow a nucleus of transformation product to occur and to grow radially at a rate G (cm/sec). In order for displacement spikes to prevent gamma-phase decomposition, it is necessary for a displacement spike to occur around the point before the nucleus has grown to a volume $1/8 v_s$, where v_s is the volume of a displacement spike. This situation is illustrated in Figure 1.

$$\frac{4}{3} \pi r_n^3 = v_n, \text{ volume of nucleus.}$$

$$\frac{4}{3} \pi r_s^3 = v_s, \text{ volume of displacement spike.}$$

$$r_s = 2 r_n$$

$$\therefore v_s = 8 v_n$$

Any spike of volume v_s whose center lies within the volume v_n will annihilate the whole nucleus. The volume of the nucleus as a function of time is given by

$$v_n = \frac{4}{3} \pi (Gt)^3 \quad (1)$$

where G is the radial growth rate, cm/sec.

The time τ required for the nucleus to grow to size $v_n = \frac{v_s}{8}$ is given by

$$\tau = \left(\frac{3}{32 \pi v_s} \right)^{1/3} \frac{1}{G} \quad (2)$$

For annihilation of the nucleus at least one displacement spike must occur in the volume described by a sphere of radius $(r_n + r_s)$ within time τ . Thus,

$$S \frac{4}{3} \pi (r_n + r_s)^3 \tau = 1 \quad (3)$$

where S = rate of spiking (number/cc/sec).

Since $r_s = 2 r_n$, and $v_s = \frac{4}{3} \pi r_s^3$, equation (3) becomes

$$\frac{27}{8} S v_s \tau = 1. \quad (4)$$

NOTE

This document is an interim memorandum prepared primarily for internal reference and does not represent a final expression of the opinion of Westinghouse. When this memorandum is distributed externally, it is with the express understanding that Westinghouse makes no representation as to completeness, accuracy, or usability of information contained therein.

The rate of spiking, S, in a given material is dependent upon the thermal neutron flux, the number of fissionable atoms per unit volume, the fission cross-section, and the number of displacement spikes per fission. This relationship is given by

$$S = \phi N \sigma \alpha \quad (5)$$

where ϕ is the thermal neutron flux,

N is the number of U-235 atoms per cm^3 of alloy

σ is the microscopic fission cross-section of
U-235 = $549 \times 10^{-24} \text{ cm}^2$

α is the number of displacement spikes per fission.
Assume = 6.

Parenthetically, it should be pointed out that the assumption of 6 displacement spikes per fission is based upon that of Bleiberg, Jones and Lustman (Phase Changes in Pile Irradiated Uranium-Base Alloys, JAP 27 (1956) 1270), in which the number of displacement spikes associated with the fission event itself is taken as 3, the number arising from neutrons born in fission as 2, and the number arising from the incident fast flux as 1. The total of 6 displacement spikes is considered to be conservative. The contribution of incident fast flux arises from the experimental situation in the MTR, in which there was net flow of fast neutrons from the adjacent parts of the test reactor to the specimen.

Combining equations (2), (4), and (5) yields the desired expression for the critical thermal neutron flux required for annihilation of nuclei.

$$\phi_c = \frac{16G}{27 N \sigma \alpha v_s} \left(\frac{4}{3} \frac{\pi}{v_s} \right)^{1/3} \quad (6)$$

Equation (6) may also be solved for $\phi N \sigma$ which is proportional to power density.

$$\phi N \sigma = \frac{16G}{27 \alpha v_s} \left(\frac{4}{3} \frac{\pi}{v_s} \right)^{1/3} \quad (7)$$

Specific power in watts/cm^3 of alloy = $s = 3.2 \times 10^{-11} \phi N \sigma$.

Calculation of Critical Flux as a Function of the Rate of Growth of a Nucleus

In calculating ϕ_c from equation (6), the following values for the quantities involved were used.

G arbitrarily assume values of 10^{-10} to 10^{-6} cm/sec

N the number of U-235 atoms per cm^3 of alloy

$$N = \frac{\rho}{\bar{A}} L (0.78) E$$

where ρ is the density of the alloy (U-10 w/o (23-a/o) Nb) taken as 16.5 gm/cc.

$\bar{A}$ is the mean atomic weight of the alloy = 206.4.

L = Avogadro's Number = 6.02×10^{23} .

(0.78) = atom fraction uranium in alloy.

$$E = \frac{\% \text{ U-235 enrichment}}{100}$$

For the U-10 w/o Nb alloy,

$$N = 0.375 \times 10^{23} E.$$

Values of E corresponding to natural U, 5, 10, 15 and 20% enrichment are assumed in the calculation.

σ is taken as $549 \times 10^{-24} \text{ cm}^2$.

α is taken as 6 spikes/fission as previously discussed.

v_s is taken as $3.3 \times 10^{-18} \text{ cm}^3$ (as in Bleiberg, Jones, and Lustman).

For the purpose of calculation, equation (6) becomes

$$\phi_c = 1.58 \times 10^{21} \frac{G}{E}.$$

The result is given below and plotted in Figure 2.

<u>E</u>	<u>G cm/sec</u>	<u>ϕ_c neutrons/cm²sec</u>
0.7	10^{-12}	2.26×10^{11}
	10^{-10}	2.26×10^{13}
	10^{-6}	2.26×10^{17}

<u>E</u>	<u>G cm/sec</u>	<u>ϕ_c neutrons/cm²sec</u>
5	10 ⁻¹²	3.16 x 10 ¹⁰
	10 ⁻¹⁰	3.16 x 10 ¹²
	10 ⁻⁶	3.16 x 10 ¹⁶
10	10 ⁻¹²	1.58 x 10 ¹⁰
	10 ⁻¹⁰	1.58 x 10 ¹²
	10 ⁻⁶	1.58 x 10 ¹⁶
15	10 ⁻¹²	1.05 x 10 ¹⁰
	10 ⁻¹⁰	1.05 x 10 ¹²
	10 ⁻⁶	1.05 x 10 ¹⁶
20	10 ⁻¹²	7.92 x 10 ⁹
	10 ⁻¹⁰	7.92 x 10 ¹¹
	10 ⁻⁶	7.92 x 10 ¹⁵

Thus, if the rate of growth of a nucleus were known, it would be possible to calculate the required rate of displacement spiking, and hence, the neutron flux to prevent transformation. In ordinary theory of nucleation and growth in solids, the rate of growth of a nucleus is not treated, and it is necessary to assume here that this rate is the same as that of the growth of the lamellar transformation product. This may not, however, be too far wrong since the displacement spike contains on the order of 10⁵ atoms, while stable nuclei are generally considered to contain about 10² atoms. Thus, in terms of the model, the growth of the nucleus to one-eighth the size of a displacement spike represents volumes larger than that of a nucleus.

Estimation of Critical Flux for U-10 w/o Nb as a Function of Temperature

Since there are practically no data on the rate of nucleation and the rate of growth for the isothermal transformation of gamma to $\delta_2 + \alpha$ in the U-10 w/o Nb alloy, it is necessary for the present to rely upon

one such measurement made at 550°C, and to estimate values at lower temperatures. It is interesting to note that the model assumes that the rate of nucleation is very high, and as a consequence, the derived expression involves only the rate of growth. Lombardo obtained a value of 5×10^{-6} cm/sec for the rate of growth at 550°C. In order to estimate the rate of growth at lower temperatures, it was assumed that the rate of growth controls the rate of transformation at temperatures below 550°C. This is generally true at temperatures below the nose of the TTT curve. From the time-temperature-transformation curve, the following data are readily determined.

<u>G cm/sec</u>	<u>T, °C</u>
5×10^{-6}	550
5×10^{-7}	440
5×10^{-8}	400
5×10^{-9}	375
5×10^{-10}	360

Using Figure 2, the critical flux for each value of G can be determined, and subsequently plotted against the temperature. The result is presented in Figure 3. The curves in Figure 3 give the value of thermal neutron flux which must be equalled or exceeded in order to prevent transformation at various irradiation temperatures. The extrapolation to temperatures below 360°C is such that the indicated fluxes are probably too high.

Figure 1

Annihilation of a Nucleus by a Displacement Spike

$G, \text{ cm/sec}$

K&E SEMI-LOGARITHMIC 359-96
KEUFFEL & ESSER CO. MADE IN U.S.A.
7 CYCLES X 60 DIVISIONS

 $G, \text{ cm/sec}$

Figure 2

403 008

MODEL

DATE

 ϕ_c , Minimum Thermal Neutron Flux For Gamma StabilityK&E SEMI-LOGARITHMIC 359-96
KEUFFEL & ESSER CO. MADE IN U.S.A.
7 CYCLES X 60 DIVISIONS

Figure 3