MAR 7 1967

0108

Report No. AGN-8214
Contract AT(04-3)-368
Project Agreement No. 6

NPS

MASTER

EVALUATION STUDY OF HASTELLOY X AS A
NUCLEAR CLADDING

Quarterly Progress Report
1 October through 31 December 1966

RELEASED FOR ANNOUNCEMENT
IN NUCLEAR SCIENCE ABSTRACTS

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency Thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

DISCLAIMER

Portions of this document may be illegible in electronic image products. Images are produced from the best available original document.

PAGE BLANK

CPSTI PRICES

N.G. \$ 3.00; MN .65

EVALUATION STUDY OF HASTELLOY X AS A
NUCLEAR CLADDING

Quarterly Progress Report
1 October through 31 December 1966

Published

February 1967

RELEASED FOR ANNOUNCEMENT
IN NUCLEAR SCIENCE ABSTRACTS

APPROVED BY: *R. H. Chesworth*

R. H. Chesworth, Manager
Nuclear Engineering and
Manufacturing Operations

LEGAL NOTICE

This report was prepared as an account of Government sponsored work. Neither the United States, nor the Commission, nor any person acting on behalf of the Commission:

A. Makes any warranty or representation, expressed or implied, with respect to the accuracy, completeness, or usefulness of the information contained in this report, or that the use of any information, apparatus, method, or process disclosed in this report may not infringe privately owned rights; or

B. Assumes any liabilities with respect to the use of, or for damages resulting from the use of any information, apparatus, method, or process disclosed in this report.

As used in the above, "person acting on behalf of the Commission" includes any employee or contractor of the Commission, or employee of such contractor, to the extent that such employee or contractor of the Commission, or employee of such contractor prepares, disseminates, or provides access to, any information pursuant to his employment or contract with the Commission, or his employment with such contractor.

NUCLEAR PRODUCTS AND SERVICES GROUP
AEROJET-GENERAL CORPORATION
SAN RAMON, CALIFORNIA

L E G A L N O T I C E

This report was prepared as an account of Government-sponsored work. Neither the United States, nor the Commission, nor any person acting on behalf of the Commission:

A. Makes any warranty or representation, expressed, or implied, with respect to the accuracy, completeness, or usefulness of the information contained in this report, or that the use of any information, apparatus, method, or process disclosed in this report may not infringe privately owned rights; or,

B. Assumes any liabilities with respect to the use of, or for damages resulting from the use of any information, apparatus, method or process disclosed in this report.

As used in the above, "person acting on behalf of the Commission" includes any employee or contractor of the Commission, or employee of such contractor to the extent that such employee or contractor of the Commission, or employee of such contractor prepares, disseminates, or provides access to, any information pursuant to his employment or contract with the Commission, or his employment with such contractor.

The information herein is regarded as preliminary and subject to further checking, verification, and analysis.

EVALUATION STUDY OF HASTELLOY X AS A
NUCLEAR CLADDING

Quarterly Progress Report
1 October through 31 December 1966

TABLE OF CONTENTS

	<u>Page</u>
I. <u>INTRODUCTION AND SUMMARY</u>	1
II. <u>TECHNICAL PROGRESS</u>	3
A. TASK A - OXIDATION STUDIES	3
1. <u>Task A-1, Low-Cobalt Tubing Control Specimen Evaluations</u>	3
2. <u>Task A-2, Commercial-Cobalt Specimen Evaluations</u>	18
3. <u>Task A-3, High Temperature Oxidation Studies</u>	25
B. MECHANICAL PROPERTIES STUDIES	29
1. <u>Task B-1, Phase I, 1800°F Tests</u>	29
2. <u>Task B-2, Phase II, 1800°F Tests</u>	36
3. <u>Tasks B-3 and B-4 - High Temperature Studies</u>	38
4. <u>Task B-3 - Adaptation of Centrifugal and Tensile Creep Apparatus for Inert Atmosphere Testing</u>	38
5. <u>Task B-4, 1300°F Creep Tests in Argon Atmosphere</u>	39
6. <u>Task B-5, 1400°F Creep Tests in Argon Atmosphere</u>	39
7. <u>Task B-6, 1700°F Creep Tests in Argon Atmosphere</u>	39
8. <u>Task B-7, 1800°F Creep Tests in Argon Atmosphere</u>	39
REFERENCES	41

PAGE BLANK

LIST OF TABLES

<u>No.</u>	<u>Title</u>	<u>Page</u>
1.	Comparison of Experimentally Determined d-Spacings for Hastelloy X (Heat E9517) Specimens Aged in Air for 10,000 Hours at 1600 and 1800°F with Published Data	5
2.	Results* of Chemical Analysis Performed on Selected Samples From Hastelloy X Heat E9517 Exposed as Indicated	17
3.	Results of Microhardness Measurements Taken on Specimens of Hastelloy X Heat X14593 Exposed in Air for 12,500 Hours	19
4.	Hastelloy X Control Specimens Analyzed by Particle Extraction and X-Ray Diffraction	20
5.	Comparison of Published and Experimentally Determined d-Spacings for Sigma Phase	22
6.	Hastelloy X Samples Submitted for Electron Microscopic Analysis	24
7.	Results* of Chemical Analyses Performed on Selected Samples of Hastelloy X Heat X14593 Exposed as Indicated	25
8.	Room Temperature Tensile Properties of Hastelloy X Specimens Exposed in Air at 2000°F	26
9.	Chemical Composition of Hastelloy X Heats	37

LIST OF FIGURES

<u>No.</u>	<u>Title</u>	<u>Page</u>
1.	Maximum Oxidation Penetration vs Aging Time for Hastelloy X (Heat X-14593)	7
2.	Maximum Oxidation Penetration vs Aging Time for Hastelloy X (Heat #9517)	8
3.	Temperature Dependence of Maximum Depth of Oxide Penetration (Hastelloy X Heat X14593)	9
4.	Temperature Dependence of Maximum Depth of Oxide Penetration (Hastelloy X Heat E9517)	10
5.	Two-Phase Oxide Formation on Specimen of Hastelloy X Heat X14593 Aged 10,000 hrs in Air at 1750°F	11
6.	Mean Values of Oxidation Penetration of Functions of Time and Temperature for Heat X14593	13

LIST OF FIGURES CONTINUED

<u>No.</u>	<u>Title</u>	<u>Page</u>
7.	Mean Values of Oxidation Penetration as Functions of Time and Temperature for Heat E9517	14
8.	X-Ray Scanning Image of Oxide Scale on Specimen of Hastelloy X (Heat E9517) Aged 10,000 hr in Air at 1750°F	16
9.	Electron Micrographs of Specimen from Hastelloy X Heat X14593 Aged 10,000 hr in Air at 1450°F	23
10.	Room Temperature Tensile Properties of Various Hastelloy X Specimens Exposed in Air at 2000°F	27
11.	Comparison of Strain vs Time for Hastelloy X Subjected to Bending and Tensile Creep at $\sigma_c = 1187$ psi	31
12.	Comparison of Strain vs Time for Hastelloy X Subjected to Bending and Tensile Creep at $\sigma_c = 1165$ psi	32
13.	Appearance of Surface Region of Hastelloy X After Bending Creep Testing	34

EVALUATION STUDY OF HASTELLOY X AS A
NUCLEAR CLADDING

Quarterly Progress Report
1 October through 31 December 1966

I. INTRODUCTION AND SUMMARY

This report has been prepared to summarize technical progress during the period from 1 October through 31 December 1966 under the program to evaluate Hastelloy X as a cladding material for nuclear fuels. The reported work is authorized by Project Agreement No. 6 of Contract AT(04-3)-368 between the USAEC and the Aerojet-General Corporation (AGC). The work was performed, primarily, at San Ramon, California, by personnel of the Nuclear Engineering and Manufacturing Operation of the Nuclear Products and Services Group of AGC.

The microconstituent analysis of both low and commercial cobalt tubing verified the presence of sigma phase in this alloy in specimens exposed at temperatures of 1300 and 1450°F. This finding contradicts statements found in the literature which establish major quantities of gamma prime $\text{Ni}_3(\text{Al,Ti})$ or eta phases as a condition necessary to formation of sigma in nickel-base alloys. The major phase that can be identified in samples exposed at temperatures in excess of 1450°F is M_6C , with lattice parameters varying between 10.927 at 1600°F and 10.977 at 1800°F. M_{23}C_6 carbides may also be present, but have not been positively identified.

The oxidation penetration data for the low and commercial cobalt tubing exposed at temperatures between 1300 and 1800°F have been analyzed to determine the time and temperature dependence of this reaction. These analyses indicate that the limiting oxygen transport mechanism changes from diffusion through the oxide film to diffusion through the metal matrix at temperatures low in this range. Regression analyses of the penetration data were performed to determine activation energies for the oxidation reaction.

Electron microprobe analyses show that the oxide film formed on Hastelloy X is composed of two layers; the outer layer is rich in manganese and chromium and has an approximate composition of MnCr_2O_4 ; the inner layer is rich in chromium alone.

Electron microscopic examination of specimens has permitted detailed analysis of the structure present in the Hastelloy X alloy. Preliminary examination of a specimen aged for 10,000 hours at 1450°F has not resulted in identification of sigma phase although these efforts are continuing.

Room temperature tensile testing of specimens exposed up to 7500 hours at 1900 and 2000°F was completed. All samples tested reached a ductility maximum after 100 hours exposure, followed (in samples from two heats) by a sharp decrease in ductility after 1000 hours. The ductility increased after this decrease until 2500 hours, after which it decreased gradually with increasing exposure. Samples from one heat did not follow this pattern but showed a gradual ductility decrease commencing after 100 hours.

Comparison of bending creep data and tensile creep data obtained on Hastelloy X materials in air at 1800°F revealed a systematic difference. The tensile creep curves are typified by initially increasing creep rates which reach a maximum depending upon applied stress. Bending creep curves follow a more classical form, having a short primary creep stage followed by an extended secondary stage. The tensile creep curves can be modified to approximate those of bending creep by removal of the surface layer (consisting of the oxide layer and layer depleted in carbide precipitates) from the test specimens. The carbide depleted layer and the oxide layer reappear in a short time and cause an increase in the creep rate. This situation is somewhat unusual since the behavior of bending creep specimens should be more sensitive to surface condition.

Centrifugal creep testing of specimens of three heats of Hastelloy X for 1000 hours in air was initiated; approximately 400 hours of testing had been accumulated by the end of the report period.

As a result of a program redirection by the Government, the centrifugal creep machine will be adapted to permit testing in a high purity inert gas. The original testing program was cancelled and a program substituted which includes testing at 1300, 1400, 1700 and 1800°F in an argon atmosphere.

II. TECHNICAL PROGRESS

A. TASK A - OXIDATION STUDIES

1. Task A-1, Low-Cobalt Tubing Control Specimen Evaluations

a. Microconstituent Extraction and Analysis

The preliminary evaluation of the microconstituent characterization data obtained to date was presented earlier*. During the report period, work was initiated on a number of specimens aged for various times at various temperatures. In addition, a more detailed analysis of the existing data was begun.

It was shown earlier* that excellent agreement exists between the experimental data developed under this program and those reported by the University of Michigan relative to the formation of the Ni-Cr-Mo type sigma phase in Hastelloy X. Additional verification of the presence of sigma phase in Hastelloy X is presented later in this report (III-A-2-e) where data from sheet material specimens aged at 1300°F in inert gas for 2680 hours are discussed.

However, two conclusions cited in the literature regarding sigma phase are, we believe, in error; these are discussed below:

(1) Experimenters at TRW report that "before sigma formation can occur in a nickel-base alloy, it is first necessary that there be copious

* "Evaluation of Hastelloy X as a Nuclear Fuel - Quarterly Progress Report, 5 July through 30 September 1966," AGN-8205.

gamma prime and/or eta precipitation".⁽¹⁾ Hastelloy X is a solid-solution strengthened alloy, and, as such, contains no gamma prime or eta precipitation and the data developed under this program clearly refutes the TRW conclusion. Other investigators have also detected sigma phase in nickel-base alloy systems, none of which contain copious gamma prime or eta precipitation.⁽²⁻⁷⁾ Apparently, the TRW experiments overlooked the possibility of sigma phase formation in other systems.

(2) It has also been reported that, at higher temperatures (presumably above 1400°F), Hastelloy X exhibits a complex microstructure consisting of intermetallics such as sigma or Laves-Type phases.⁽⁸⁻¹¹⁾ The analysis of more than 30 X-ray diffraction patterns of residues extracted from Hastelloy X specimens (representing six different heats, two exposure environments, two fabrication variables and aging temperatures between 1300 to 1850°F for durations up to 12,500 hours) produced to date under this program has not resulted in the positive identification of any intermetallics occurring above 1450°F. Representative X-ray diffraction patterns, obtained from residues extracted from specimens of Hastelloy X (Heat E9517) exposed in air for 10,000 hours at 1600 and 1800°F, are compared with published data for M_6C -type carbides, Laves Phase (Fe_2Mo), and $M_{23}C_6$ -type carbides in Table 1. It can be seen that the primary constituent present in both samples is M_6C with a lattice parameter which varies from 10.927Å at 1600°F to 10.977Å at 1800°F. It is also apparent that the fit of major peaks for Laves Phase is poor; a better fit is displayed for $M_{23}C_6$ and M_6C -type carbides. Supporting evidence for this observation was reported earlier by Wagoner,⁽¹²⁾ who showed that the major constituents present in Hastelloy X after 500 hours exposure at 1600 and 1800°F were M_6C and $M_{23}C_6$ carbides. In addition, the examination of the microstructure of Hastelloy X specimens exposed at temperatures in excess of 1450°F would certainly reveal the presence of intermetallics; the only intermetallic that has been identified in samples examined in this program was sigma phase and this occurred only in specimens exposed at temperatures less than 1450°F.

(1) Superscript numbers in parenthesis refer to references listed at the end of this report.

TABLE 1

COMPARISON OF EXPERIMENTALLY DETERMINED d-SPACINGS FOR HASTELLOY X (HEAT E9517)
SPECIMENS AGED IN AIR FOR 10,000 HOURS AT 1600 AND 1800°F WITH PUBLISHED DATA

EXPERIMENTAL DATA									
1600°F		1800°F		M ₆ C*		Laves Phase ⁽⁹⁾		M ₂₃ C ₆ ⁽⁹⁾	
dÅ	Rel. Int.	dÅ	Rel. Int.	dÅ	I/I _i	dÅ	I/I _i	dÅ	I/I _i
		3.11	5	3.14	20				
2.71	15	2.73	10	2.72	50				
		2.67	10	2.56	10			2.66	50
		2.51	35	2.50	50				
2.37	25			2.31	50	2.36	60	2.38	100
2.23	50	2.24	55	2.22	80				
2.17	15			2.16	60	2.18	100	2.17	100
2.09	100	2.10	100	2.10	100	2.05	60		
2.02	10			2.05	50	2.02	100	2.05	100
1.92	25	1.94	30	1.92	80	1.98	60		
1.82	10	1.82	10	1.81	40			1.80	100
1.52	10	1.54	10	1.52	50				
1.42	10	1.43	10	1.43	20	1.37	60		
1.33	10			1.33	50	1.33	60		
1.29	30	1.29	30	1.29	30	1.29	100	1.29	75
1.26	5	1.27	5	1.27	20			1.25	75
1.22	5			1.22	50			1.23	100
1.19	10	1.10	10	1.15	30	1.18	60	1.19	75
1.09	10	1.08	5	1.09	65				

* ASTM Index Card #11-546

b. Oxidation Characteristics

A summary of the average maximum depth of oxidation penetration measured in the various samples currently under investigation is shown in Figure 1 for specimens from Heat X14593, and in Figure 2 for specimens from Heat E9517. The time and temperature dependence of these penetrations is illustrated in Figures 3 and 4. The major difference between the two heats appears in the penetration data at short times and low temperatures, where the rate limiting step is apparently changing from one oxygen transport mechanism to another. However, the temperature dependence at times greater than 2500 hours for Heat E9517 and 5820 hours for Heat X14593 is very similar.

In general, it appears (Figures 3 and 4) that the oxide penetration mechanism is changing at 1300°F. At this temperature, the oxidation mechanism is believed to consist of two basic steps: (1) diffusion of oxygen through the oxide scale, and (2) penetration of oxygen through the matrix with the resultant internal oxidation. This may account for the significant difference in penetration time dependence between 1300 and 1600°F or above. This difference is more prominent for Heat E9517 than that for Heat X14593. At higher temperatures (above 1450°F), penetration becomes almost negligible in Heat E9517 after 5000 hours and in Heat X14593 after 10,000 hours.

On the basis of the oxidation penetration model discussed above, the rate limiting step for 100 hour data would be diffusion of oxygen through the oxide scale. At longer times and higher temperatures, however, the rate limiting step would be oxygen diffusion through the metal matrix. This hypothesis implies that the oxide scale has become less coherent, and has broken sufficiently to present no barrier to oxygen transport into the exposed metal substrate.

One interesting feature of the oxide film morphology observed is shown in Figure 5. Here, the oxide is revealed as a two-phase structure (Figure 5a), the outer layer of which is apparently brittle in comparison to the inner layer (Figure 5b).

FIGURE 1. MAXIMUM OXIDATION PENETRATION VERSUS AGING TIME FOR HASTELLOY X (HEAT X14593)

FIGURE 2. MAXIMUM OXIDATION PENETRATION VERSUS AGING TIME FOR HASTELLOY X (HEAT E 9517)

17.1-67-076

FIGURE 3. TEMPERATURE DEPENDANCE OF MAXIMUM DEPTH OF OXIDATION PENETRATION HASTELLOY X (HEAT X14593)

FIGURE 4. TEMPERATURE DEPENDENCE OF MAXIMUM DEPTH OF OXIDATION PENETRATION HASTELLOY X (HEAT E 9517)

AGN-8214

(a) Uniform, Adherent Outer Layer

(b) Discontinuous and Broken Outer Layer

FIGURE 5. TWO-PHASE OXIDE FORMATION ON SPECIMEN OF HASTELLOY X HEAT X 14593 AGED 10,000 hr IN AIR AT 1750°F

25,77-66-1368

The outer layer of this duplex oxide has been identified, using electron microprobe techniques (discussed later), as a manganese compound. It is uncertain whether the Mn layer is present on specimens aged at lower temperatures and/or shorter times, since investigations in this area have not yet been commenced. Extensive metallographic preparation, including deposition of a nickel coating on the surface of the specimen prior to preparation, was required to reveal the Mn layer. The nickel coating is necessary to retain the (apparently) brittle Mn layer, which scales off during post-test handling and subsequent metallographic processing.

The oxidation data presented in Figures 6 and 7 were treated in another manner which involved the use of a high speed digital computer. The arithmetic means of the penetration measurements taken at each temperature-time combination were fit to the expression:

$$\text{Log Penetration} = \text{Log Time} + \Delta H/RT + \text{Constant} \quad (1)$$

by means of a least-squares multiple-regression program, i.e., the equation of the plane for the least-squares fit through the three-dimensional time-temperature-penetration space was derived. The analysis of the 25 values from Heat X14593 by this technique produced the family of curves shown as dashed lines in Figure 6 and the treatment of the 20 values from Heat E9517 yielded the family of dashed lines in Figure 7.

Because the two-dimensional penetration-time data appeared to have a different slope at higher temperatures than at lower, the data were reanalyzed in two parts: the data for the three higher temperatures were analyzed separately from those for the lower two temperatures. In both cases, the regression lines for the higher temperature data had smaller slopes than those for the lower temperature data, suggesting a different mechanism. The solid lines in Figures 6 and 7 represent the results of the two-part analysis.

The activation energies (enthalpies) for oxidation obtained from Equation 1 were found to be -16.3 and -29.7 kcal/mole for the high and low temperatures of Heat E9517, respectively, and -18.0 and -22.9 kcal/mole for the high and low temperatures of Heat X14593. No particular significance can be ascribed to these activation energies at present since

FIGURE 6. MEAN VALUES OF OXIDATION PENETRATION AS FUNCTIONS OF TIME AND TEMPERATURE FOR HEAT X14593

FIGURE 7. MEANS VALUES OF OXIDATION PENETRATION AS FUNCTIONS OF TIME AND TEMPERATURE FOR HEAT E 9517

the method used in the derivation differed from that normally employed in oxidation calculations. Earlier work performed by Wlodek⁽¹³⁾ and Aerojet* on the oxidation of Hastelloy X yielded activation energies of 60 Kcal/mole and 63 Kcal/mole, respectively. The derivation of activation energies in these earlier studies, however, was based on continuous weight change data, obtained for the continuous build-up of a surface oxide film. The present calculations were obtained using internal oxide penetration data, the oxidation mechanism for which is considered different from that which occurs during uniform surface bulk oxidation.

This regression analysis is incomplete since penetration measurements used were an average of four taken for each specimen following each exposure condition (time-at-temperature). It is planned to analyze each data point independently to develop more accurate and reliable least-squares fits. In addition, more meaningful extrapolations of oxidation penetrations to longer times and higher temperatures can be performed, and more accurate activation energies can be determined which will help characterize the oxidation behavior of the alloy.

c. Microprobe and Electron Microscopy Analyses

Electron microprobe analysis of a specimen from Heat E9517, exposed in air at 1600°F for 10,000 hours, was completed. The results of this analysis were being evaluated at the end of the report period. Preliminary observations indicate that the outer portion of the duplex oxide (discussed earlier) is a Mn-rich layer with an approximate composition of MnCr_2O_4 (spinel). A similar Mn-rich layer is depicted in Figure 8, which shows a scanning image of the oxide scale on a specimen from Heat E9517 aged in air at 1750°F for 10,000 hours. The manganese reaches a maximum content of 21 wt% in the outer portions of the oxide scale.

These findings are in contrast to work performed at GE-FPD,⁽¹⁴⁾ where the Mn content of oxide films on Hastelloy X exposed 100 hours at 2000°F was reported to be 6%. An understanding of this difference

* Aerojet-General Nucleonics, San Ramon, California, Army Gas-Cooled Reactor Systems Program, "Isothermal Oxidation of Hastelloy X at 1750 and 1850°F in Air," AGN TM-413, (1965).

on, 25 kv

Magnification 1300X

AGN-8214

FIGURE 8. X-RAY SCANNING IMAGE OF OXIDE SCALE ON SPECIMEN OF HASTELLOY X HEAT E 9517 AGED 10,000 HOURS IN AIR AT 1750°F

is considered significant since the Mn content of the oxide film may relate to the corrosion resistance of the alloy. X-ray diffraction studies performed earlier by Aerojet* on a number of alloys (including Hastelloy X) aged at 1850°F, indicated that only the oxide films on Hastelloy X contained the Mn constituent. Further investigations are planned to verify these findings; microprobe analyses of specimens exposed at different temperatures and times will be performed in an effort to resolve the observed inconsistencies.

d. Chemical Analysis

Selected samples of low-cobalt control specimens were chemically analyzed for boron, oxygen, nitrogen and carbon using emission spectrographic techniques. The results of these analyses are summarized in Table 2. The expected trends were observed; the carbon content remained relatively unchanged and the nitrogen and oxygen contents generally increased with increasing time and temperature. Two of the nitrogen analyses (samples G-1 and -2) are unreasonably high; these results are believed to be artifacts of the analysis procedures.

TABLE 2

RESULTS* OF CHEMICAL ANALYSIS PERFORMED ON SELECTED SAMPLES
FROM HASTELLOY X HEAT E9517 EXPOSED AS INDICATED

Sample No.	Exposure Conditions			Wt %			B, ppm
	Atm.	Time, hrs	Temp., °F	C	N ₂	O ₂	
G-15	As-Rec.; Unexposed			0.111	0.029	0.003	--
G-1	Air	10,000	1300	0.110	0.215	0.110	--
G-2	"	"	1600	0.115	0.207	0.109	--
G-3	"	"	1750	0.108	0.098	0.314	17
G-4	"	5000	1300	0.109	0.052	0.133	--
G-5	"	"	1600	0.108	0.045	0.165	--
G-6	"	"	1750	0.105	0.061	0.396	--

* Experimental Accuracies:

O ₂	± 10 ppm
N ₂	± 10 ppm
C	± 5 ppm
B	± 1 ppm

* AGN Report No. AN-1464, Advanced Alloys Testing Program, Evaluation of Potential High Temperature Cladding Alloys, Project Final Technical Report, October 1965.

e. Evaluation of Mechanical Properties Data

Room temperature mechanical properties data were discussed earlier.* Elevated temperature tensile tests were initiated during and were in progress at the end of the current report period.

f. Effect of Heat Treatment on Sigma Phase

Work under this sub-task was not initiated during the report period.

g. Effect of Sigma Phase on Mechanical Properties

Work under this sub-task was not initiated during the report period.

2. Task A-2, Commercial-Cobalt Specimen Evaluations

a. Metallographic Evaluation of Air-Exposed Tubing

The results of these evaluations were reported earlier*; no further reports will be made of activity under this sub-task.

b. Metallographic Examination of Inert-Gas Exposed Material

The results of these evaluations were reported earlier*; no further reports will be made of activity under this sub-task.

c. Tensile Testing

The results of room temperature tensile tests were reported earlier*. Elevated temperature tensile tests were initiated during the current report period and were in progress at the end of December.

d. Hardness Tests

Microhardness measurements were taken on specimens of Heat X14593 exposed in air for 12,500 hours. The results of these measurements are presented in Table 3. The values listed are an average of at least three impressions taken at the inner diameter (ID), the center, and the outer diameter (OD) of each tubing specimen. A general trend is apparent in which

* AGN-8205, Evaluation Study of Hastelloy X as a Nuclear Cladding, Quarterly Progress Report 5 July through 30 September 1966, (1966).

TABLE 3

RESULTS OF MICROHARDNESS MEASUREMENTS TAKEN ON SPECIMENS OF
HASTELLOY X HEAT X14593 EXPOSED IN AIR FOR 12,500 HOURS

Sample No.	Temp., °F	Knoop Hardness Number			Ave.
		ID	Center	OD	
As-Received					250
F ₃ O-0	1300	236	273	232	247
E ₃ -9-9	1450	227	276	219	241
E ₃ -9-8	1600	229	282	223	245
E ₃ -9-7	1750	202	236	192	210
E ₃ -9-6	1800	212	256	198	222

the hardness decreases with increasing temperature. Also, the OD and ID regions are softer than the tubing center, an effect not unexpected based upon past observations. All values shown are consistently lower than those measured for the material from Heat X14593 in the as-received condition.

e. Microconstituent Extraction and Analysis

The results of the microconstituent extraction and X-ray diffraction analyses discussed earlier* are presented in Table 4. As indicated in this Table, second phases for which a positive identification was made are labeled (S), those phases which are probably present are labeled (W), and those for which a very weak pattern was obtained, indicating a possibility of their presence, are labeled (VW); X-ray diffraction patterns which were unidentifiable were not listed. The data include all of the samples electrolytically digested in HCl, and a few of those extracted using H₃PO₄. Most of the patterns obtained from the H₃PO₄ extractions were considerably different from those obtained using HCl and have not yet been identified. A more detailed analysis will be presented in a later report. As discussed earlier*, identifications were made by comparison with X-ray diffraction patterns currently available in the literature.

* AGN-8205

TABLE 4

HASTELLOY X CONTROL SPECIMENS ANALYZED BY PARTICLE EXTRACTION AND X-RAY DIFFRACTION

Sample No.	Heat No.	Mat'l Type	Exposure History			Extraction Electrolyte	Phases Present*
			Atm.	Temp., °F	Time, hrs		
1H	X4762	Sheet	Inert Gas	1300	2680	HCl	(S) M_6C ; (VW) $M_{23}C_6$
1P	X4762	"		"	"	H_3PO_4	(VW) $M_{23}C_6$
2H	X34381	"		"	"	HCl	(S) M_6C ; (VW) $M_{23}C_6$
2P	X34381	"		"	"	H_3PO_4	(S) M_6C ; (W) $M_{23}C_6$; (VW) σ
3H	E9505	"		"	"	HCl	(S) M_6C ; (S) σ ; (VW) $M_{23}C_6$
4	E9505	"		"	100	"	(W) M_6C ; (VW) $M_{23}C_6$
5	X4762	"		"	"	"	(W) M_6C ; (VW) $M_{23}C_6$
6	X34381	"		"	"	"	(W) M_6C ; (VW) $M_{23}C_6$
7H	X4762	"		1850	2680	"	(S) M_6C ; (VW) $M_{23}C_6$
8H	E9505	"		"	"	"	(S) M_6C ; (W) $M_{23}C_6$
9H	X34381	"		"	"	"	(S) M_6C
10	X4762	"		"	100	"	(S) M_6C
11	E9505	"		"	"	"	(S) M_6C
12	X34381	"		"	"	"	(S) M_6C ; (W) $M_{23}C_6$
13	E9517	Tubing		1300	2680	"	(S) M_6C ; (S) σ ; (W) $M_{23}C_6$
14	X14593	"		"	1000	"	(S) M_6C ; (W) σ
15H	X34381	Sheet		"	"	"	(S) M_6C
15P	X34381	"		"	"	H_3PO_4	(S) M_6C
16	E9505	"		"	"	HCl	(W) M_6C
17H	E9522	"		"	"	"	(S) M_6C
18H	X4762	"		"	"	"	(S) M_6C

Table 4 continued

Sample No.	Heat No.	Mat'l Type	Exposure History			Extraction Electrolyte	Phases Present*
			Atm.	Temp., F	Time, hrs		
18P	X4762	Sheet	Inert Gas	1300	1000	H ₃ PO ₄	(S) M ₂₃ C ₆
19	E9517	Tubing	↓	"	"	HCl	(S) M ₆ C
20	X14593	"		"	"	"	(S) M ₆ C
21H	E9505	Sheet		1850	"	"	(S) M ₆ C
22H	X4762	"		"	"	"	(S) M ₆ C
23	X34381	"		"	"	"	(S) M ₆ C
24	E9522	"		"	"	"	(S) M ₆ C
25	E9517	Tubing		"	"	"	(S) M ₆ C
26	X14593	"		"	"	"	(S) M ₆ C

- * S = Strong pattern (positive identification)
W = Medium to weak pattern (phase probably present)
VW = Very weak pattern (possibility of phase being present)

Sigma phase (Ni-Cr-Mo type) was also detected in a few of the residues of specimens aged in inert gas at 1300°F. Representative d-spacings for two of these samples are shown in Table 5 and compared to published d-spacings for a Ni-Cr-Mo type sigma phase.

TABLE 5
COMPARISON OF PUBLISHED AND EXPERIMENTALLY
DETERMINED d-SPACINGS FOR SIGMA PHASE

<u>Published Data</u> (2)		<u>Sample 3H*</u>		<u>Sample 13**</u>	
<u>dÅ</u>	<u>I/I_i</u>	<u>dÅ</u>	<u>I/I_i</u>	<u>dÅ</u>	<u>I/I_i</u>
2.47	VW	2.495	10	2.494	15
2.39	W	2.368	10	2.367	10
2.29	MW	2.309	10	Conflict	
2.15	MS	2.159	30	2.160	10
2.09	M	2.088	100	2.092	100
2.04	M	2.047	10	2.025	10
1.995	MS	1.995	25	1.995	10
1.955	MS	1.955	30	1.959	10
1.91	MS	1.912	20	1.920	25

* Heat E9505 (Sheet) Aged 2680 hours in inert gas at 1300°F (HCl Extraction)

** Heat E9517 (Tubing) Aged 2680 hours in inert gas at 1300°F (HCl Extraction)

f. Microprobe and Electron Microscopy Analyses

Electron microprobe analyses were completed on a specimen of Heat X14593 aged in air and on a specimen of Heat E9517 aged in inert gas. The results of these analyses were being evaluated at the end of the report period.

Electron microscopy was also completed on a specimen of Heat X14593 aged 10,000 hours in air at 1450°F. A carbon replica was obtained from the metallographically prepared specimen surface and was subsequently shadowed at 20° with Pt/Pd. The resultant prepared replica was examined using a Phillips Model EM-100 electron microscope. Micrographs representing the structure observed are shown in Figure 9. A grain boundary region is shown in Figure 9a, while a twin-boundary area is displayed in Figure 9b. The large particles shown at the boundaries in both micrographs

(a) 6000X - Grain Boundary Region

(b) 8000X - Twin Boundary Region

FIGURE 9. ELECTRON MICROGRAPHS OF SPECIMEN FROM HASTELLOY X
HEAT X14593 AGED 10,000 HOURS IN AIR AT 1450°F

17.1-67-081

are believed to be M_6C -type carbides. Carbides of the $M_{23}C_6$ -type, if present, usually are found at the boundary regions,⁽¹⁵⁾ and could appear as the small particles in between the larger M_6C particles in Figure 9a. The identification of the very small discrete particles dispersed within the grain interiors is not known at present; however, contemplated electron diffraction analysis should assist in obtaining a positive identification.

No evidence of sigma phase precipitation was observed in the microscopy performed. Sigma phase normally occurs as needles or Widmanstätten type precipitates in nickel-base alloys.⁽¹⁶⁾ The techniques used in performing the reported microscopy examinations are not considered optimum, however, since etchants and replicating techniques for Hastelloy X are currently in the experimentation stages. Additional work in this area should be more fruitful in defining the sigma phase or other phases present.

Three additional specimens were being analyzed by electron microscopy techniques at the end of the report period; the history of these specimens is shown in Table 6. In addition to performing the usual electron microscopic examination, a carbon extraction replica will be obtained from sample Q₂-0-9 and electron diffraction analysis conducted on the extracted particles.

TABLE 6

HASTELLOY X SAMPLES SUBMITTED FOR ELECTRON
MICROSCOPIC ANALYSIS

Sample Number	Heat Number	Exposure History		
		Atm.	Temp., °F	Time, hrs
Q ₂ -0-9	E9517	Air	1300	2500
E ₃ -5-1	E9517	Inert Gas	1300	2680
V ₂ -5-4	X14593	Air	1750	10,000
V ₂ -5-3	X14593	Air	1600	10,000

g. Chemical Analysis

The results of chemical analysis performed on selected samples from Heat X14593, which were aged in air, are summarized in Table 7. As with specimens discussed earlier (II-A-1-d), the carbon content remained

fairly constant while the nitrogen and oxygen contents generally increased with increasing time and temperature.

TABLE 7

RESULTS* OF CHEMICAL ANALYSES PERFORMED ON SELECTED SAMPLES OF
HASTELLOY X HEAT X14593 EXPOSED AS INDICATED

Sample No.	Atm.	Temp., °F	Time, hrs	Wt %			B, ppm
				C	N ₂	O ₂	
G-7	Air	1300	12,500	0.080	0.029	0.027	--
G-8	"	1600	"	0.083	0.057	0.322	--
G-9	"	1750	"	0.086	0.075	0.403	14
G-10	"	1300	5820	0.100	0.024	0.021	--
G-11	"	1600	"	0.098	0.022	0.246	--
G-12	"	1750	"	0.092	0.036	0.397	--

* Experimental Accuracies:

O ₂	± 10 ppm
N ₂	± 10 ppm
C	± 5 ppm
B	± 1 ppm

3. Task A-3, High Temperature Oxidation Studies

a. Metallographic Evaluation

Metallographic examination of sheet specimens aged in air for 7500 hours at 1900 and 2000°F was initiated late in the report period.

b. Room and Elevated Temperature Tensile Tests

Room temperature tensile testing of sheet specimens aged in air at 2000°F for 7500 hours was completed. The results of these tests, together with results obtained earlier for specimens aged for 100, 1000, 2500 and 5000 hours, are presented in Table 8 and plotted in Figure 10. The ultimate tensile strengths after each exposure are quite similar for all three heats and reveal a decrease in strength with increasing exposure up to 5000 hours, after which there is little additional change.

TABLE 8

ROOM TEMPERATURE TENSILE PROPERTIES OF HASTELLOY X SPECIMENS EXPOSED IN AIR AT 2000°F

Heat No.	Exposure Time, Hrs	UTS, psi	Tensile Properties	
			0.2% Offset YS, psi	% Elong. in 1-inch
X4762	As-Received	114,400	60,000	40.4
E9505	"	109,700	59,000	35.5
X34381	"	123,000	77,800	35.8
X4762	100	98,500	-	40.8
E9505	100	100,200	-	40.0
X34381	100	97,200	-	40.6
X4762	1000	86,500	-	20.3
E9505	1000	96,300	-	38.0
X34381	1000	96,900	-	18.8
X4762	2500	82,900	34,600	33.7
E9505	2500	83,200	35,600	33.1
X34381	2500	81,500	34,200	28.0
X4762	5000	74,500	31,100	26.4
E9505	5000	74,900	28,900	27.4
X34381	5000	73,900	37,000	22.3
X4762	7500	75,900	32,800	20.6
E9505	7500	73,300	39,500	23.4
X34381	7500	73,900	35,600	12.5

FIGURE 10. ROOM TEMPERATURE TENSILE PROPERTIES OF VARIOUS HASTELLOY X SPECIMENS EXPOSED IN AIR AT 2000°F

All three heats reach a ductility maximum after 100 hours of exposure. This is followed by a sharp decrease in ductility for heats X4762 and X34381 after 1000 hours, an increase in ductility for these two heats after 2500 hours and then a gradual decrease with increasing exposure. Heat E9505 did not exhibit a loss of ductility after 100 hours but showed a continued gradual decrease in ductility with increasing exposure duration.

A complete analysis of the tensile data and the correlations of these data with microstructure will be undertaken to give meaning to the ductility behavior described.

Elevated temperature tensile tests were in progress at the end of the report period.

c. Microconstituent Extraction and Characterization

No work was performed under this sub-task during the report period.

d. X-Ray Analysis of Surface Oxide

No work was performed under this sub-task during the report period.

e. Electron Microprobe and Microscopic Analysis

No work was performed under this sub-task during the report period.

f. Chemical Analysis

No work was performed under this sub-task during the report period.

g. Thermo-Gravimetric Tests

No work was performed under this sub-task during the report period.

B. MECHANICAL PROPERTIES STUDIES

1. Task B-1, Phase 1 1800°F Tests

a. Bending Creep Data Analysis

The reduction and analysis of the bending creep data generated in tests of specimens from Heats E9505 and 4762 tested at 1800°F in air using the centrifugal creep technique was reported earlier*; no further reports of activity under this sub-task will be made.

b. Tensile Creep Tests

The apparatus, test procedures, test conditions, and test data for the tensile testing were discussed earlier.* In an effort to resolve differences between the bending creep data and tensile creep data, an additional specimen of Heat 4762 and two additional specimens of Heat 9505 were tested in tensile creep. The surfaces of these specimens was removed by milling to duplicate the surface conditions and the thickness (0.045") of the bending creep specimens.

The raw tensile creep data obtained during the test was in the form of gauge section elongation as a function of time. The elongation was divided by the initial gauge length to determine the engineering strain. The data were reduced and a plot of strain versus time produced; these curves are shown in Figures 11 and 12.

c. Comparison of Bending and Tensile Creep Data

A topical report was published in November discussing the comparison between bending and tensile creep data.** As indicated in this report, comparison of the strain versus time curves for constant load tensile creep and bending creep reveals a systematic difference. The tensile creep curves are typified by initially increasing creep rates that appear to reach a maximum rate depending on the applied stress. The bending creep curves, on the other hand, indicate a very short primary creep stage and an extended secondary creep stage. Experimental procedures in both techniques have been

* AGN-8205

** Correlation of Tensile and Bending Creep Data for Hastelloy X, AGN-8203.

FIGURE 11. COMPARISON OF STRAIN VERSUS TIME FOR HASTELLOY X
SUBJECTED TO BENDING AND TENSILE CREEP AT $\sigma_c = 1187 \text{ psi}$

FIGURE 2 COMPARISON OF STRAIN VERSUS TIME FOR HASTELLOY X SUBJECTED TO BENDING AND TENSILE CREEP AT $\sigma_c = 1165 \text{ psi}$

thoroughly reviewed and the observed systematic differences are true indications of differing creep behavior under the two applied stress conditions.

The appearance of an outer layer in the test material in the as-received condition and after 1645 hours and 333 hours of bending creep testing in air is shown in Figure 13. It is clear from these photomicrographs that a precipitate-depleted layer exists in the as-received material. Therefore, removal of several mils of material from the surface of such a specimen results in a condition where the outer layer has essentially the same microstructure as the remainder of the specimen. However, photos of such specimens after 1645 and 333 hours show that an oxide layer and the precipitate-free outer layer reforms and increases in depth with exposure time. These photos also show that microstructural changes occur in the outer layer which appear to be different from those which occur in the bulk of the material. It is reasonable to expect that the different changes in the two regions will effect creep differently.

Specifically, the absence of the precipitate-depleted layer during the early stage of a test would effect bending creep characteristics more than tensile creep characteristics because of the significant dependence of bending creep data on outer fiber strength. Microstructural changes, occurring with time and exposure at test temperature, would effect tensile creep properties most because these properties depend, primarily, on the behavior of the core of the material. One would then expect that if the precipitate-depleted layer is not present at the beginning of tests of both types, the creep behavior would be nearly the same for bending and tensile creep and that differences in behavior would appear as the layer forms and core microstructural changes occur. This, unfortunately, does not separate the effect, if any, associated with the formation of the oxide layer as the test proceeds.

It is clear from the data presented in Figures 11 and 12 that removal of the precipitate-free layer from the as-received sheet causes the tensile specimens to creep in a manner similar to the bending creep specimens and that, after the precipitate-free layer has reformed, the tensile creep data deviates from the bending creep data and from data for the bending creep test of specimens from which the surface layer was not removed. The

(a) As-Received Heat E9505

(b) After 164.5hr Bending Creep Testing at 1800°F
Heat X4762 with Pre-Test Heat Treatment

(c) After 333hr Bending Creep Testing at 1800°F with Pre-Test Heat Treatment

FIGURE 13 . APPEARANCE OF SURFACE REGION OF HASTELLOY X
AFTER BENDING CREEP TESTING

37.31-66-1344

data do not permit a conclusion regarding which testing mode (bending or tensile creep) is most effected by the surface layer or which data describe the normal creep behavior of this alloy. The presence of a precipitate-depleted layer, however, causes an initially increasing creep rate in the tensile specimens as shown in Curves 3 and 5 in Figure 11 and Curve 3 in Figure 12. Curve 3 of Figure 11 and Curve 2 of Figure 12 show that, some time after the precipitate-free layer has reformed, the tensile creep rate again deviates markedly from the bending creep rate. Comparison of the creep of heat-treated specimens to that of as-received specimens shows that, for both tensile and bending creep, the material in the as-received condition is markedly stronger, irrespective of the presence or absence of the precipitate-free layer.

Examination of the photomicrographs shows that carbides do not coalesce at the grain boundaries in the outer layers. In addition, no convincing evidence of ductile microcracks could be found. Since all specimens were taken from immediately adjacent portions of the material, it does not seem likely that compositional or structural variations within the sheet could be responsible for the difference in bending and tensile creep behavior. Work in another portion of this program has shown that the precipitate-free layer forms only during oxidation; specimens exposed at elevated temperatures in inert gas do not form a precipitate-depleted layer. The present data do not permit a separation of the effects of oxide layer from the effect of the associated precipitate-depleted layer on the creep properties.

The following conclusions are drawn from the data presented in Figures 11, 12, and 13.

- 1) The presence of the precipitate-free outer layer and associated oxide layer on the tensile creep specimens is apparently responsible for the initial difference between tensile creep rates and bending creep rates. If this layer is absent, initial tensile creep rates are similar to initial bending creep rates.
- 2) A significant difference in the creep rates under bending stress and under tensile stress may or may not exist after some creep has occurred. The data of Figures 11 and 12 indicate that the final creep rate for both tensile and bending creep tests is nearly

the same for specimens with the same thermal history.

3) Important design implications are associated with this experimental observation; the data indicate that wide variations in creep rates will occur depending on the stress state of a component. Consequently, in design situations where bending will occur, creep rates can be expected which are considerably in excess of those predicted from conventional creep data determined by tensile techniques. In view of these implications, it is important that an understanding of the influence of microstructure and other factors on the creep properties of the alloy be developed.

d. Activation and Stress Dependency for Creep

The redirection of the mechanical properties study (see Section I) has eliminated the 1900°F creep tests. Only very limited data is available from the 1800°F tests for a meaningful computation of the activation energy. This analysis has been postponed until completion of the 1800°F test now in progress.

The stress dependence for creep for the data obtained to date (not including the test in progress) was reported earlier*. As soon as the test now in progress is completed, the stress dependence for Hastelloy X Heats 4793, 4787 and 4902 will also be computed and reported.

2. Task B-2, Phase II, 1800°F Tests

a. Complete 1800°C Centrifugal Creep Tests

Centrifugal creep testing of specimens from three additional heats of Hastelloy X (4793, 4787 and 4902) for 1000 hours in air was initiated. At the end of the report period, this test had accumulated approximately 400 hours; completion is scheduled at the end of January, 1967. The chemical composition of the material is presented in Table 9. Each heat

* AGN-8205.

TABLE 9

CHEMICAL COMPOSITION OF HASTELLOY X HEATS

Heat No.	Element, wt %											
	Cr	W	Fe	C	Si	Co	Ni	Mn	Mo	P	S	B
X2-4902	22.41	0.01	17.98	0.10	0.74	0.07	49.43	0.58	8.66	0.013	0.006	0.002
X5-4793	21.73	0.69	18.10	0.08	0.86	1.80	47.28	0.61	8.86	0.034	0.006	
X5-4787	21.38	0.58	18.60	0.05	0.72	1.94	47.35	0.56	8.80	0.016	0.003	

is being tested at four stress levels corresponding to approximately 0.1, 0.2, 0.5 and 1% total strain. Comparison of total deflection vs time for the three heats at the end of the report period indicates that the behavior of Heats 4902 and 4793 is nearly the same, while Heat 4787 is weaker by a factor of about 2.

b. Tensile Creep Tests

The tensile creep testing of two specimens from one of the heats tested in bending creep (see above) will be initiated as soon as the bending creep data are collected and reduced. These tests will be performed in air at 1800°F.

c. Comparison of Tensile and Bending Creep Data

This work will be performed as soon as data from Task b above is available.

3. Tasks B-3 and B-4 - High Temperature Studies

The work originally contemplated under these tasks was cancelled by the program redirection (see Section I). Inert atmosphere creep studies were substituted for the cancelled tasks; progress under these tasks is reported below.

4. Task B-3 - Adaptation of Centrifugal and Tensile Creep Apparatus for Inert Atmosphere Testing

a. Adaptation of Centrifugal Creep Apparatus

The design of modifications to the centrifugal creep testing apparatus to permit testing in a high purity inert gas atmosphere at temperatures up to 1800°F was initiated. The modifications include the provision of a vessel, fabricated of Hastelloy X, which completely encloses the rotating head and test specimens. The viewing windows, for observing specimen deflections, will extend about 8 inches above and below the existing furnace and will be water-cooled to permit the use of "O" ring seals around the quartz windows. A large tube will be welded at the bottom of the vessel. This tube will also be water-cooled since it encases the rotating head shaft and rotating seal. The seal to the shaft will be an asbestos-graphite labyrinth type. Connections for evacuating the vessel, for the introduction of argon gas, and for the sampling of atmosphere throughout the duration of the

test will also be provided.

b. Adaptation of Tensile Creep Apparatus

The redirected program includes tensile creep correlation tests in high purity argon. Two of the existing USAEC-owned Arc-Weld tensile creep machines will be modified to perform these tests. The procurement of two Arc-Weld (Satec) vacuum-retort-argon furnaces was initiated as was the procurement of optical apparatus for reading specimen elongation.

5. Task B-4, 1300^oF Creep Tests in Argon Atmosphere

Work has not been initiated on this task.

6. Task B-5, 1400^oF Creep Tests in Argon Atmosphere

Work has not been initiated on this task.

7. Task B-6, 1700^oF Creep Tests in Argon Atmosphere

Work has not been initiated on this task.

8. Task B-7, 1800^oF Creep Tests in Argon Atmosphere

Work has not been initiated on this task.

REFERENCES

1. H. E. Collins, Research on Microstructural Instability of Nickel-Base Superalloys, Interim Engineering Progress Report No. 1, TRW Report ER6960 for the period 1 July 1966 - October 1966.
2. "Relations Between Microstructure and Creep Rupture Properties of Nickel-Base Alloys as Revealed by Over-Temperature Exposures," University of Michigan Report NASA-TN-D-1325, Sept. 1962.
3. C. J. Bechtoldt and H. C. Vacher, "Phase Diagram Study of Alloys in the Iron-Chromium-Molybdenum-Nickel System," Journ. Res. Nat. Bur. Stds., Vol. 58, Research Paper 2728, Jan. 1957.
4. S. P. Rideout and P. A. Beck, "Survey of Portions of the Cr-Co-Ni-Mo Quaternary System at 1200°C," NACA-TN-2683, Univ. of Notre Dame, Apr. 1952.
5. K. Kuo, "Ternary Laves and Sigma Phases of Transition Metals," Acta. Met., Vol. 1, p. 270, 1953.
6. D. K. Das, S. P. Rideout and P. A. Beck, "Intermediate Phases in the Mo-Fe-Co, Mo-Fe-Ni and Mo-Ni-Co Ternary Systems," Trans. of the Met. Soc. AIME, Vol. 194, p.1071, 1952.
7. V. H-J. Schuller, P. Schwaab and K. Albrecht, "Untersuchungen über das Ausscheidungsverhalten Von Sonderlegierungen auf der Basis Nickel-Molybdän und Nickel-Molybdän-Chrom," Z. Metallkde. B.O. 57 (1966) H.4, p. 312.
8. F. A. Comprelli and U. E. Wolff, Stability of High-Nickel Alloys in Superheated Steam, GEAP-4745, Nov. 1964.
9. F. A. Comprelli and J. E. Lewis, Microstructural Evaluation of Superheat Cladding Materials, GEAP-4751, Jan. 1965.
10. T. T. Claudson, Quarterly Progress Report - Metallurgy Research Operation Hanford Laboratories, October - December 1963, Report HW-79766, Jan. 15, 1964.
11. J. E. Antill, et al., Oxidation of Some Nickel Base Alloys in Carbon Dioxide at 900-1000°C, GCM/UK/B13, January 1965.
12. E. L. Wagoner, Physical Metallurgy and Mechanical Properties of Hastelloy Alloy X, Haynes Stellite Company, Kokomo, Indiana, June 23, 1961.
13. S. T. Wlodek, "The Oxidation of Hastelloy Alloy X," Trans. Met. Soc. AIME, V. 230, Feb. 1964, p. 177.

14. Nickel-Base Superalloy Oxidation, GE-FPD Report DM 66-304, Interim Progress Report No. 2, for the Period January 1, 1966 - June 30, 1966.
15. C. P. Sullivan and M. P. Donachie, Jr., Some Effects of Microstructure on The Mechanical Properties of Nickel-Base Superalloys, ASM Tech. Rep. No. C6-18.2. Presented at the 1966 National Metal Congress, Oct. 31. - Nov. 3, 1966, Chicago, Ill.
16. W. J. Boesch and J. S. Slaney, "Preventing Sigma Phase Embrittlement in Nickel Base Superalloys," Metal Progress, July 1964, p. 109.

DISTRIBUTION LIST

CONTRACT NO. AT(04-3)-368, PROJECT AGREEMENT NO. 6 WITH AEROJET

U. S. Atomic Energy Commission
San Francisco Operations Office
2111 Bancroft Way
Berkeley, California

U. S. Atomic Energy Commission (2)
Division of Reactor Development
and Technology
Washington, D. C.
Attn: J. M. Simmons

U. S. Atomic Energy Commission
Division of Reactor Development
and Technology
Washington, D. C.
Attn: A. Van Echo

U. S. Atomic Energy Commission
Division of Reactor Development
and Technology
Washington, D. C.
Attn: Dr. J. A. Lieberman

U. S. Atomic Energy Commission
Division of Reactor Development
and Technology
Washington, D. C.
Attn: S. A. Szawlewicz

U. S. Atomic Energy Commission
Division of Reactor Development
and Technology
Washington, D. C.
Attn: M. J. Whitman

U. S. Atomic Energy Commission
Office of Space Nuclear Systems
Washington, D. C.
Attn: F. D. Haines

U. S. Atomic Energy Commission
Office of Space Nuclear Systems
Washington, D. C.
Attn: F. C. Schwenk

U. S. Atomic Energy Commission
Office of Space Nuclear Systems
Washington, D. C.
Attn: R. T. Carpenter

U. S. Atomic Energy Commission
Office of Space Nuclear Systems
Washington, D. C.
Attn: C. E. Johnson

U. S. Atomic Energy Commission
Division of Reactor Development
and Technology
Washington, D. C.
Attn: R. E. Pahler

U. S. Atomic Energy Commission
Division of Reactor Development
and Technology
Washington, D. C.
Attn: D. E. Bailey

U. S. Atomic Energy Commission (3)
Division of Technical Information
Extension
Box 62
Oak Ridge, Tennessee 37831
Attn: R. L. Shannon

U. S. Atomic Energy Commission
Document Library
Germantown, Maryland 20545

Argonne National Laboratory
9700 South Cass Avenue
Argonne, Illinois
Attn: R. E. Macherey

Argonne National Laboratory
9700 South Cass Avenue
Argonne, Illinois
Attn: L. Kelman

Argonne National Laboratory
9700 South Cass Avenue
Argonne, Illinois
Attn: J. H. Kittel

Distribution List for Contract AT(04-3)-368 (continued)

Brookhaven National Laboratory
Upton, Long Island, New York 11973
Attn: D. Gurinsky

Brookhaven National Laboratory
Upton, Long Island, New York 11973
Attn: C. Klamut

Los Alamos Scientific Laboratory (2)
P. O. Box 1663
Los Alamos, New Mexico
Attn: D. B. Hall

Oak Ridge National Laboratory (2)
P. O. Box Y
Oak Ridge, Tennessee
Attn: J. Cunningham

Oak Ridge National Laboratory
P. O. Box Y
Oak Ridge, Tennessee
Attn: P. Patriarca

Oak Ridge National Laboratory
P. O. Box Y
Oak Ridge, Tennessee
Attn: J. Weir

Pacific Northwest Laboratory (2)
Battelle Memorial Institute
P. O. Box 999
Richland, Washington
Attn: J. J. Cadwell

Pacific Northwest Laboratory
Battelle-Memorial Institute
P. O. Box 999
Richland, Washington
Attn: T. T. Claudson

U. S. Air Force
Code MATB
Wright-Patterson AFB, Ohio
Attn: G. Glenn

Army Materials Research Agency
Watertown Arsenal
Watertown 72, Massachusetts
Attn: S. V. Arnold

NASA-Lewis Research Center
21000 Brookpark Road
Cleveland, Ohio 44135
Attn: G. M. Ault

NASA-Lewis Research Center
21000 Brookpark Road
Cleveland, Ohio 44135
Attn: T. Moss

NASA
Code RRM
Washington, D. C. 20546
Attn: J. Maltz

Bureau of Naval Air Systems
Department of the Navy
Washington, D. C.
Attn: I. Machlin

Atomics International
Division of North American Aviation
P. O. Box 309
Canoga Park, California
Attn: C. E. Weber

Babcock and Wilcox Company
1201 Kemper Street
Lynchburg, Virginia
Attn: C. Baroch

Combustion Engineering, Inc.
P. O. Box 5000
Windsor, Connecticut 06095
Attn: W. P. Chernock, Asst. Mgr.,
Nuclear Laboratories

Combustion Engineering, Inc.
P. O. Box 5000
Windsor, Connecticut 06095
Attn: S. S. Christopher
Nuclear Laboratories

General Atomic
Division of General Dynamics
P. O. Box 1111
San Diego, California 92112
Attn: A. Weinberg

Distribution List for Contract AT(04-3)-368 (continued)

General Electric Company
Nuclear Materials & Propulsion Op.
Evendale, Ohio
Attn: J. McGurty

General Electric Company
Nuclear Materials & Propulsion Op.
Evendale, Ohio
Attn: C. Brassfield

General Electric Company (3)
310 DeGuigne Drive
Sunnyvale, California 94086
Attn: K. P. Cohen, Gen. Mgr.,
Advanced Products Operation

MSA Research Corporation
Callery, Pennsylvania
Attn: C. H. Staub

MSA Research Corporation
Callery, Pennsylvania
Attn: R. C. Werner

Nuclear Materials and
Equipment Corporation
609 N. Warren Avenue
Apollo, Pennsylvania 15613
Attn: Z. M. Shapiro, President
& General Manager

United Nuclear Corporation
5 New Street
White Plains, New York 10601
Attn: Dr. K. Goldman

United Nuclear Corporation
P. O. Box 1583
365 Winchester Avenue
New Haven 4, Connecticut
Attn: A. Strasser

Westinghouse Electric Corporation
Atomic Power Division
P. O. Box 355
Pittsburgh, Pennsylvania 15230
Attn: Dr. J. H. Wright, Mgr.,
Advanced Reactor Systems

Westinghouse Electric Corporation
Atomic Power Division
P. O. Box 355
Pittsburgh, Pennsylvania 15230
Attn: R. J. Allio, Mgr.
Advanced Materials

Westinghouse Electric Corporation
P. O. Box 10864
Pittsburgh, Pennsylvania 15236
Attn: D. Goldberg
Astro Nuclear Laboratory

Battelle-Memorial Institute
Columbus, Ohio
Attn: DMIC

Battelle-Memorial Institute
Columbus, Ohio
Attn: S. Paprocki

Lockheed Aircraft Company
Palo Alto, California
Attn: R. A. Perkins

Boeing Airplane Company
Aero-Space Division
P. O. Box 3707
Seattle, Washington
Attn: J. T. Stacey

McDonnell Aircraft Company
Department 272
P. O. Box 516
St. Louis, Missouri
Attn: H. Siegel

Union Carbide Satellite Company
Kokomo, Indiana
Attn: W. Schussler

Sandia Corporation
P. O. Box 5800
Albuquerque, New Mexico 87115
Attn: R. P. Stromberg
Division 9333