97,696

INTERATOMIC POTENTIALS AND DEFECT ENERGETICS
IN DILUTE ALLOYS

by

Paul S. Ho
IBM Thomas J. Watson Research Center
Yorktown Heights, New York 10598

Roy Benedek
Department of Materials Science and Engineering
Cornell University, Ithaca, New York 14850

December 20, 1973
Cornell University
Ithaca, New York

NOTICE

This report was prepared as an account of work sponsored by the United States Government. Neither the United States nor the United States Atomic Energy Commission, nor any of their employees, nor any of their contractors, subcontractors, or their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness or usefulness of any information, apparatus, product or process disclosed, or represents that its use would not infringe privately owned rights.

Report #2158
Issued by
The Materials Science Center

MASTER

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency Thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

DISCLAIMER

Portions of this document may be illegible in electronic image products. Images are produced from the best available original document.

INTERATOMIC POTENTIALS AND DEFECT ENERGETICS
IN DILUTE ALLOYS

by

Paul S. Ho
IBM Thomas J. Watson Research Center
Yorktown Heights, New York 10598

Roy Benedek
Department of Materials Science and Engineering
Cornell University, Ithaca, New York 14850

ABSTRACT: Effective interatomic potentials for impurities in aluminum have been constructed according to the pseudopotential theory. Based on a local model potential, impurity valence and size factors have been defined and their effects on the potential are discussed. Using these potentials, detailed calculations based on a Green's function lattice statics method have been made for the impurity-vacancy binding energy and the difference in diffusion activation energies for an impurity and a host atom. The results can account satisfactorily for the experimental data of nontransition impurities, but less so for the noble-metal impurities. Contributions from the lattice relaxation energies are important, particularly for impurity migration. Dielectric screening of the ion by the conduction electrons is important in determining the potential and must be properly accounted for in calculating the energetics for impurities.

I. INTRODUCTION

Atomic diffusion in dilute alloys is strongly influenced by the nature of the interaction between vacancies and solute atoms. This diffusion plays an important role in many solid state phenomena. The formation of precipitates which contribute to alloy strengthening is one example having considerable practical importance.¹ The phenomenon of impurity segregation to grain boundaries and voids is another example. It is therefore of some interest to obtain a quantitative understanding of the vacancy-impurity interaction. The physical parameters of primary interest in this regard are the binding energy for vacancy-solute pairs and jump frequencies for vacancy migration in the vicinity of a solute atom.

The purpose of the present paper is to develop an approach for the calculation of these parameters and to apply it to impurity diffusion in aluminum, for which extensive experimental data are available. Such calculations require i. interatomic potentials describing the host-host and host-impurity interactions and ii. a procedure for including the effect of the lattice relaxation surrounding the point defect configurations. An impurity is commonly characterized by its valence and "size". We have therefore attempted to vary these parameters in a systematic way to determine their effects on the energetics of the vacancy-impurity interaction.

This paper is divided into two parts. The first part describes the construction of the interatomic potential within the framework of pseudopotential theory. Based on a local model potential, size and

valence factors are defined and their effect on the pair potentials is discussed. The second part deals with the calculation of the impurity-vacancy binding energy and the difference in diffusion activation energies for an impurity and a host atom. Here, considerable effort has been spent in the calculation of lattice relaxation energies. For this purpose the Green's function formulation of lattice statics² has been used. The results, particularly for migration energies, show that lattice relaxation has a large effect.

Nontransition impurities in aluminum were chosen as the subject of numerical calculations. This choice was motivated by the validity of the pseudopotential approach for aluminum and also the existence of some recent data for impurity diffusion and vacancy-solute binding energies.³ For simplicity, we have limited our study to nontransition impurities. Transition impurities, which have been found to have quite different diffusion behavior in aluminum, should be an interesting subject for future study.

II. INTERATOMIC POTENTIALS

Interatomic potentials for aluminum alloys are developed here within the framework of pseudopotential theory. In previous studies^{4,5} of vacancy-impurity interactions, interatomic potentials calculated from somewhat less detailed models e.g. the Fermi-Thomas and Friedel potentials, have been used. While the validity of the pseudopotential approach to describe lattice defects has not been rigorously established,⁶ this approach does represent a more serious attempt at a realistic theory than those used in previous work. Pseudopotential theory

has at least two advantages over the above mentioned models:

- i. the nonrealistic point ion model is avoided and ii. the effect of electron gas exchange and correlation on the screening are included at least approximately.

In this section the pseudopotential formulation of interatomic potentials is reviewed, and a discussion of the local model potential used in numerical calculations is given.

Consider a simple metal characterized by a nearly free electron valence band. Its total energy can be divided according to pseudopotential theory into volume dependent and structure dependent parts.⁷ The former includes the kinetic, exchange and correlation energies for a uniform electron gas plus the first-order correction from the electron-ion interaction. This part can be written as a function of the average electron density and is essential for maintaining the lattice equilibrium. The second part depends on the detailed atomic arrangement. It consists of the direct electrostatic interaction between ions, and the indirect ion-ion interaction through the screening of the conduction electrons. The latter is called the band structure energy and for pure metals can be expressed as⁸

$$U_{BS} = \frac{N}{2\Omega} \sum_{k \neq 0} \frac{k^2}{2\pi} |V_1(k)|^2 S(k) \left(\frac{1}{\epsilon_k} - 1 \right)$$

where Ω is the atomic volume, N is the total number of ions, $V_1(k)$, called the strength function by Shaw,⁹ is the Fourier transform of the bare model potential of the ion, $S(k)$ is the structure factor, ϵ_k

is the dielectric function and the sum extends over all reciprocal lattice vectors. Combining the ion-ion coulomb potential with U_{BS} one can express the structure dependent energy in terms of an effective potential $\phi(r)$ given by⁸

$$\phi(r) = \frac{Z_1^2 e^2}{r} \left[1 - \frac{2}{\pi^2} \int_0^\infty \left(\frac{k^2 v_1(k)}{4\pi Z_1 e^2} \right)^2 \left(\frac{1}{\epsilon_k} - 1 \right) \frac{\sin kr}{k} dk \right]$$

A similar derivation can be carried out for a dilute alloy and one arrives at an effective potential between A and B ions of the form⁸

$$\phi_{AB}(r) = \frac{Z_a Z_b e^2}{r} \left[1 - \frac{2}{\pi^2} \int_0^\infty \left(\frac{k^2 v_a(k)}{4\pi Z_a e^2} \right) \left(\frac{k^2 v_b(k)}{4\pi Z_b e^2} \right) \left(\frac{1}{\epsilon_k} - 1 \right) \frac{\sin kr}{k} dk \right] \quad (2.1)$$

where the subscripts refer to the two types of ions. In the dilute limit ϵ_k is simply the dielectric function for the pure host metal.

The separation of the total crystal energy into volume and structure dependent parts is very convenient for defect calculations in metals. In fact the parameters which we wish to calculate, i.e., binding energies and migration energies, may be expressed in terms of structural energies alone, as is shown in the appendix. In the calculation described in sections III and IV, we require the pair potentials $\phi_{AA}(r)$ and $\phi_{AB}(r)$. The remainder of this section is concerned with the determination of these quantities and particularly with the dependence of $\phi_{AB}(r)$ on the size and valence of the impurity.

To construct the interatomic potentials, we require the explicit form of the pseudopotential for the host and impurity ions. As in

previous work¹⁰ we adopt a local potential having a simplified Heine-Abarenkov¹¹ form:

$$V_i(r) = \begin{cases} -V_i & r < R_m^i \\ -\frac{Z_i e^2}{r} & r > R_m^i \end{cases}$$

Here i stands for either an impurity or a host atom. This model potential contains two parameters: V_i , the potential well depth and R_m^i , the model radius of the ion. The Fourier transform of $V_i(r)$ is

$$V_i(k) = \frac{-4\pi Z_i e^2}{\Omega k^2} \left[(1-\alpha_i) \cos kR_m^i + \frac{\alpha_i}{R_m^i} \frac{\sin kR_m^i}{k} \right] \quad (2.2)$$

where $\alpha_i \equiv V_i R_m^i / Z_i e^2$. α is a measure of the well depth relative to the electrostatic potential at R_m . Its value varies according to the particular model used for the local potential, e.g. $\alpha = 0$ for the Ashcroft "empty-core" potential and $\alpha = 1$ for Shaw's optimized model potential. In the present work α was fitted to give agreement with the elastic constants of Al.

On the basis of this expression for $V_i(k)$ one may discuss the effect of valence and ionic size on the interatomic potential. The term in the brackets depends only on the parameters α and R_m while the other term depends only on the ionic charge. One can consider these terms to describe respectively the "size" and valence effects on the interatomic potential. Substituting equation (2.2) into equation (2.1) one observes that $\phi_{AB}(r)$ simply scales with the valence of the impurity. Changes in the impurity size may be simulated by changes

in the model radius R_m^i while keeping the parameter α the same as that of the host atom. The "size" factor, as defined by R_m^i in our model, is incorporated into the bare ion model potential. Since the interatomic potential is obtained by screening the bare ion potential, the effect of the impurity size depends also on the extent of the dielectric screening. This places the size effect on a framework quite different from some of the earlier models¹² which treat primarily the elastic interaction between the defects.

In general, of course, α may also vary. However, appropriate values of the parameters α and R_m for specific impurities are not presently known. Therefore we attempt to ascertain in a general way the effects of size and valence of the impurity on diffusion without specifying explicitly which impurity is being considered.

$\phi_{AB}(r)$ for impurities with model radius 10% larger and smaller than the host, along with $\phi_{AA}(r)$ for aluminum is shown in Fig. 1. The impurity potentials are seen to have forms similar to that of the host-host potential and exhibit oscillations starting at the third neighbor position. In the present calculations, the potentials are truncated at the fifth neighbor position. The exact form of the potential is extremely sensitive to the particular dielectric function used, as recently emphasized by Duesbery and Taylor.¹³ The importance of the dielectric screening is underlined by the fact that even at the first neighbor position the effective interaction $\phi_{AA}(r)$ is reduced by 99.7% from the bare Coulomb interaction. The choice of the

dielectric function is therefore critical for the construction of the interatomic potential. In the present work, the dielectric function of Geldart and Taylor¹⁴ has been employed. These authors have computed electron gas exchange and correlation contributions in such a way that the important compressibility sum rule is satisfied. Our pseudopotential parameters for aluminum, $R_m = .71 \text{ \AA}$ and $\alpha = .42$, have been determined by fitting to the measured elastic constants. Phonon dispersion curves and vacancy formation and migration energies calculated on the basis of this pseudopotential are in good agreement with experimental values.

Comparing the potentials in Fig. 1, one observes a systematic change in the amplitude and phase of the oscillation as a function of the model radius. The potential for the smaller ion has weaker oscillations and a more advanced phase. This reflects a more complete screening of a smaller ion than a larger one. The overall difference in the magnitudes of the potentials is quite small, which again results from the completeness of the dielectric screening.

III. Relaxation Calculation

In the calculation of lattice relaxation and relaxation energies, the Green's function formulation of lattice statics² was employed. In this approach, certain lattice dynamical techniques are applied in the zero frequency limit to obtain the static equilibrium configuration of atoms around a point defect. A brief outline of the Green's function method and how it applies to the particular defect configurations of interest in this work is given in this section.

As in the harmonic approximation of lattice dynamics one expands

the crystal energy to second order in the atomic displacements:

$$\phi = \phi_0 - \sum_{l,\alpha} F_\alpha(l) u_\alpha(l) + \frac{1}{2} \sum_{\substack{l,l' \\ \alpha\beta}} \phi_{\alpha\beta}(l, l') u_\alpha(l) u_\beta(l') \quad (3.1)$$

Here $u_\alpha(l) = r_\alpha(l) - R_\alpha(l)$ is the displacement of atom l from its unrelaxed position (i.e., a perfect lattice site unless l corresponds to an interstitial). The coefficients $F_\alpha(l)$ and $\phi_{\alpha\beta}(l, l')$ are determined from the interatomic potentials.

The equilibrium condition $\frac{\partial \phi}{\partial u_\alpha(l)} = 0$ may be expressed in matrix form as

$$\phi u = F$$

or

$$u = \phi^{-1} F \equiv GF \quad (3.2)$$

The central problem in this approach is that of inverting ϕ to obtain the Green's function G .

Any point defect may be considered to be some combination of n_v vacancies and n_i interstitials. We will refer to each particular case by the shorthand notation (n_v, n_i) . For example: vacancy, (1,0); interstitial (0,1); "activated" or migrating vacancy, (2,1); etc. The n_v vacancies and n_i interstitials comprise the defect "core".

It is convenient to divide ϕ into two parts,

$$\phi = \phi_0 - \delta\phi \quad (3.3)$$

where $-\delta\phi$ is essentially the change in ϕ caused by the introduction of

the defect. The matrix ϕ and the vectors u and F in equation (3.2) are of dimension $D = 3(N+n_i)$ where N is the total number of lattice sites. The matrix ϕ_0 takes account only of the interactions present in the perfect crystal. $-\delta\phi$ is the change in ϕ which occurs upon "turning on" the interactions of the n_i interstitial atoms and "turning off" the interactions corresponding to the n_v vacant sites. This procedure for splitting ϕ is illustrated schematically in Fig. 2 for the case of an impurity at the saddle point, i.e. (2,1). For simplicity, only the (111) plane with nearest neighbor interactions is shown. In the calculation of ϕ_0 the interstitial atoms are treated as noninteracting free particles. $-\delta\phi$ accounts for the interactions of the impurity atom and the "turning off" of the interactions for the vacant site at the origin.

The substitution of equation (3.3) into equation (3.2) yields

$$G = (1 - G^0 \delta\phi)^{-1} G^0 = G^0 + G^0 \delta\phi G \quad (3.4)$$

where $G^0 \equiv (\phi^0)^{-1}$.

Equation (3.4) is the familiar Dyson equation for the Green's function. The methods for solving this equation are described in detail by Tewary² and therefore will only be discussed in general terms here. Two features simplify the analysis. First, the assumption of finite range interatomic interactions (in the present calculations we consider interactions extending to fifth nearest neighbors) implies that only a small number of the coefficients $P_\alpha(l)$ and $\delta\phi_{\alpha\beta}(l, l')$ are nonzero. By

employing the procedure of matrix partitioning¹⁵ to equation (3.2) one obtains the relation

$$u_p = g f \quad (3.5)$$

where

$$g = g^0 + g^0 \delta \phi_p g.$$

Equation (3.5) governs the displacements of atoms in the "perturbed space", which consists of the defect core plus the n_c lattice atoms which interact directly with the core (for the configuration shown in Fig. 2, $n_c = 116$). The matrices g , g^0 and $\delta \phi_p$ and the vectors u_p and f are of dimensions $3n_p$ where $n_p = n_i + n_v + n_c$.

Once g has been determined, displacements of atoms outside the perturbed space may also be calculated.¹⁵ However, this is not necessary if one is only interested in the relaxation energy. Substituting equation (3.2) into equation (3.1), one may express the relaxation energy as

$$E_R = \phi - \phi_0 = -Fu + \frac{1}{2} u \phi u = -\frac{1}{2} Fu = -\frac{1}{2} f u_p \quad (3.5)$$

The second simplifying feature derives from the symmetry of the lattice relaxation field. Some of the atomic displacements $u_\alpha(l)$ are equal to others by virtue of this symmetry and therefore the number of degrees of freedom in the perturbed space is less than $3n_p$. This allows one to obtain a "reduced" version of equation (3.4):

$$u^r = g^r f^r \quad (3.6)$$

Here the reduced vectors and matrices are defined by the relations

$$u_i^r = \sum_{\alpha} \psi_{\alpha}^i(l) u_{\alpha}(l) \quad (3.6a)$$

$$f_i^r = \sum_{\alpha} \psi_{\alpha}^i(l) f_{\alpha}(l) \quad (3.6b)$$

$$g_{ij}^r = \sum_{\substack{l, l' \\ \alpha, \alpha'}} \psi_{\alpha}^i(l) g_{\alpha\beta}(l, l') \psi_{\beta}^j(l') \quad (3.6c)$$

where the ψ^i are "basis" vectors in the perturbed space. The number of distinct basis vectors having the proper symmetry is equal to n_r , the number of degrees of freedom in the perturbed space. The perturbed space displacements are related to the u_i^r by the inversion formula

$$u_{\alpha}(l) = \sum_i^{n_r} \psi_{\alpha}^i(l) u_i^r \quad (3.7)$$

The reduced Green's function is determined from the Dyson equation

$$g^r = [(1 - g^o \delta\phi)^r]^{-1} g^{or} \equiv (A^r)^{-1} g^{or} \quad (3.8)$$

Equation (3.5) in conjunction with equations (3.6-3.8) provides a means for calculating relaxation energies. The defect configurations for which we require relaxation energies are illustrated in Figs. 3 and 5 and are discussed in detail in section IV and V. We wish here to point out that for each configuration the defect core may be found by inspection. Migrating atoms at saddle point sites and impurity

atoms are treated formally as interstitials.[†] A substitutional impurity is treated as an interstitial superimposed on a vacancy. For example, substitutional impurity atom, (1,1); migrating impurity atom (ω_2 jump), (2,1); dissociative jump configuration (ω_3 jump), (3,2); etc. Once the defect core for a particular configuration is identified and the appropriate interatomic potentials are specified, the calculation of the relaxation energy may proceed as we have outlined in this section.

Finally, some technical details should be mentioned here. The dimension $3n_p$ of the perturbed space is typically large enough so that direct multiplication to obtain the product $g^o \delta\phi$ in equation (3.8) is quite time-consuming even when performed on a computer. It is somewhat more convenient to compute the matrix A^r from the relation

$$A^r = \tilde{A}^r + \delta A^r \quad (3.9)$$

where

$$\tilde{A}^r = 1 - g^{or} \delta\phi^r \quad (3.9a)$$

$$\delta A_{ij}^r = - \sum_{l\alpha} \sum_{l'\alpha'} \sum_{l''\beta}^{n_v} \psi_{\alpha}^i(l) g_{\alpha\beta}^o(l, l'') \delta\phi_{\beta\alpha}(l'', l) \psi_{\alpha'}^j(l') \quad (3.9b)$$

The reduced matrices g^{or} and $\delta\phi^r$ are defined in analogy to g^r in equation (3.6c). In equation (3.9b) the l'' sum includes the n_v core vacancies.

The basis vectors ψ possess no nonzero elements in the space of the core vacancies. Therefore, the contribution to A^r due to these vacancies

[†]An impurity atom is treated formally as an interstitial even if it occupies a substitutional site since its force constants differ from those of the host.

is accounted for explicitly in the term δA^r . In the case of a monovacancy or a substitutional impurity it is easy to show that $\delta A^r = 0$ as a consequence of the inversion symmetry about the defect site. For more complicated configurations δA^r is in general nonzero and must be accounted for.

In the lattice statics calculations performed in this work pairs of atoms were assumed to interact via central forces. In this model, the ϕ matrix may be expressed in terms of the first two derivatives of the interatomic potential:

$$\phi_{\alpha\beta}(l, l') = \left(-\delta_{\alpha\beta} + \frac{r_{\alpha} r_{\beta}}{r^2} \right) \frac{1}{r} \frac{d\phi(r)}{dr} - \frac{r_{\alpha} r_{\beta}}{r^2} \frac{d^2\phi(r)}{dr^2}, \quad l' \neq l$$

$$\phi_{\alpha\beta}(l, l) = - \sum_{l' \neq l} \phi_{\alpha\beta}(l, l')$$

where $\vec{r} = \vec{R}(l) - \vec{R}(l')$ and $\phi(r)$ is the interatomic potential connecting atoms l and l' .

IV. IMPURITY-VACANCY BINDING ENERGY

Figure 3b illustrates a vacancy-impurity pair in the nearest neighbor configuration while Fig. 3a shows such a pair separated by a large distance. The binding energy E_b is the difference[†] in the crystal energies for these two configurations. In the appendix we show that this difference may be expressed in terms of pair interactions alone. It is convenient to divide the binding energy into two parts; one, which

[†] We adopt the usual sign convention for the binding energy; E_b is positive if the crystal has lower total energy in the nearest neighbor configuration.

we call E_b^C , corresponds to the unrelaxed lattices, while the other, E_b^R , accounts for the lattice relaxation. Referring to Figs. 3a and 3b, the "configuration" energy E_b^C may be written down immediately:

$$E_b^C = \phi_{AB}(r_1) - \phi_{AA}(r_1)$$

where r_1 is the nearest neighbor distance. The calculation of E_b^R is more involved since it requires the application of the lattice statics method described in the previous section to obtain the relaxation energies for the pair, the isolated vacancy and the substitutional impurity. If these energies are called respectively E_R^{vs} , E_R^v and E_R^s , one may write

$$E_b^R = E_R^s + E_R^v - E_R^{vs}$$

The calculation of the first two terms is relatively easy since $n_r = 7$, and $\delta A^r = 0$. The calculation of E_R^{vs} is more difficult, however, since $n_r = 96$ and $\delta A^r \neq 0$. A useful self-consistency check on the latter calculation is available. If the solute is treated as simply another host atom in the impurity-vacancy pair calculation, one should obtain results identical to those for the isolated vacancy. This was in fact verified in our calculations.

In Fig. 4 is illustrated the displacement field in a (111) plane containing a vacancy-impurity pair, for an impurity of valence 4. As required, the displacements exhibit axial symmetry about the vacancy-

impurity line. The magnitude of the individual atomic displacement reflect the extra attraction associated with the impurity; compare, for example, the 2.8% inward displacement of the $\overline{110}$ atom with the 3.4% displacement of the impurity.

In Table I, the results of the binding energy calculation are given. For impurities which differ only in valence from the host, the binding energy results primarily from E_b^C . However, the relaxation energy E_b^R is not negligible and it always reduces E_b . The sign of E_b depends on the sign and magnitude of $\phi_{AA}(r_1)$ which in turn depends on the dielectric screening. In the present case, since $\phi_{AA}(r_1)$ is positive, a divalent impurity is repelled by the vacancy and a negative E_b is expected. The opposite situation exists for a quadravalent impurity. For impurities differing only in size from the host, E_b^R is quite important relative to E_b^C as one can see from the results in Table I. The sign of E_b for such impurities depends on the balance of E_b^C and E_b^R .

Overall, the binding energies are quite small. It is possible to obtain an upper bound for the binding energy of impurities by setting E_b^C equal to $\phi_{AA}(r_1)$ and ignoring the contribution from the relaxation energy. Based on the effective potential for Al in Fig. 1, this upper limit is estimated to be 0.1 eV. This value, of course, depends on the dielectric function used in calculating the potential. However, judging from the magnitude of other Al potentials e.g. those derived by Duesbery and Taylor¹³ and Shyu et al.,¹⁶ the value of 0.1 eV appears to be a valid estimate.

V. ACTIVATION ENERGY FOR IMPURITY DIFFUSION

The kinetics for impurity diffusion in an fcc lattice has been studied by Howard and Manning.¹⁷ Figures 5a and 5b depict the various atomic jumps entering their model. The ratio of the diffusivities of the impurity and the host atom can be expressed as¹⁷

$$\frac{D_b}{D_a} = \left(\frac{f_b}{f_a}\right) \left(\frac{\omega_2}{\omega_0}\right) \left(\frac{\omega_4}{\omega_3}\right)$$

where the first term is the ratio of the correlation factors, the second term is the ratio of the frequencies of the saddle-point jumps for the impurity and the host and the last term is the ratio of the associative and dissociative jump frequencies for the vacancy-impurity pair. The second term is related to the migration energy difference and the third to the binding energy. One can write the difference in the diffusion activation energies as¹⁸

$$\Delta Q = \Delta E - E_b - k \frac{\partial \ln f_b}{\partial \left(\frac{1}{T}\right)} \quad (5.1)$$

where ΔE is the difference in migration energies for the impurity and the host atom and the last term arises from the temperature dependence of the correlation factor for the impurity. The last factor can be calculated from the temperature dependence of the jump frequencies in the kinetic model. Peterson and Rothman⁴ estimated it to be very close to zero for monovalent and divalent impurities in Al, independent of whether the electrostatic model or the oscillatory potential is used.

These authors also reported a preliminary measurement of this factor for Zn isotopes and found a small value of less than 0.1 eV. For simplicity, we assume this factor to be zero here.

In analogy to our treatment of the impurity binding energy, ΔE may be divided into a "configuration" contribution ΔE_c associated with the unrelaxed saddle-point configurations and a contribution ΔE_R resulting from lattice relaxation. In calculating ΔE_c or ΔE_R , one has to account not only for the different saddle-point configurations but also the different initial lattices. Thus,

$$\Delta E_R = [E_R^S(\omega_2) - E_R^{VS}] - [E_R(\omega_0) - E_R^V]$$

where the relaxation energies are associated respectively with the impurity saddle point, impurity-vacancy pair, host-atom saddle point and isolated vacancy. A similar expression exists for ΔE_c .

In Table II, numerical values calculated for ΔE are presented. It is found that the value of ΔE_c is determined mainly by the sign and magnitude of ϕ_{AA} at the distance from the saddle-point to one of the four "ring" lattice sites. In the present calculation, ϕ_{AA} at that distance is positive, therefore, a divalent impurity interacts less strongly with its surrounding atoms than a host atom because of its smaller valence. This gives rise to a negative ΔE_c . A similar situation exists for the homovalent impurity with model radius smaller than the host. The contribution from relaxation energies is observed to be comparable to that from ΔE_c and therefore must be

carefully calculated to ensure a reliable value for ΔE .

Table III gives results for ΔQ , neglecting the final term in equation (5.1). Comparing the values of ΔE and E_b , one observes that the size and valence have a larger effect on impurity migration than on binding energies.

VI. DISCUSSION

It is interesting to compare the present results with available data on the binding energy and activation energy for nontransition impurities in Al. In doing so, it is important to keep in mind since our calculations do not specify particular impurities, the comparison is only semi-quantitative in nature. Furthermore, it is difficult to extrapolate our results to very different impurity parameters. In a recent review by Balluffi and Ho,³ it was noted that the equilibrium experiments, such as the lattice expansion and positron annihilation measurements, give binding energies systematically lower than those obtained from quenching-annealing experiments. Our results seem to support the small binding energies obtained from the equilibrium measurements. For some impurities, the agreement is even quantitative; for example, Si has a valence of 4 and a E_b of .03 eV¹⁹ and Mg is divalent and its E_b was measured to be $-0.1 \pm .04$ eV²⁰ or $< .05$ eV.²¹

In Fig. 6 we list experimental values of ΔQ for three solute pairs (Cu,Ag), (Zn,Cd) and (Ga,In) together with values of R_m for various elements recently determined by Shaw.^{4†} In view of their model

† Shaw determined these R_m values based on his optimized model potential which in its local form is equivalent to setting α unity. As a result, his R_m value for Al is considerably larger than ours.

radii, the homovalent pair (Ga,In) should be almost equal in size to Al, and therefore their ΔQ values are expected to be quite small. This is consistent with the experimental results. For the divalent pair (Zn,Cd), the valence effect is expected to dominate in Zn since its R_m is nearly equal to that of Al; on this basis a negative ΔQ is predicted. For Cd, which is larger than Zn, the size effect is expected to compensate the valence effect. These predictions appear to be in accord with experimental data; ΔQ for Cd is larger than for Zn and has the opposite sign. However, our calculated ΔQ appear to exceed the measured values. The same line of reasoning fails when applied to the monovalent noble metal pair (Cu,Ag). Ag is larger than Cu and is therefore expected to have a higher ΔQ contrary to experimental observation. Thus, our calculation does not seem to account even qualitatively for the behavior of noble metal impurities. This is not surprising since the applicability of a simple model potential to d band metals is questionable.

In the forgoing discussion, we have taken the model radius R_m rather than, say its Pauling ionic radius R_i (c.f. Fig. 6) to represent the impurity "size". The former parameter is a characteristic of the metallic state and is therefore more appropriate in the present context. One may note in Fig. 6 that in certain cases a large discrepancy exists between R_m and R_i . For example, the series of trivalent elements Al, Ga, In and Tl have almost equal model radii but their ionic radii vary by almost a factor of two.

In view of model radii plotted in Fig. 6, the monovalent pair Na and K and the divalent pair Be and Mg appear to be interesting elements for experimental study. All of these can be classified as typical simple metal ions and the model radii of the two members of each pair are quite different. At present, there are no reliable diffusion data for these impurities in Al.

Finally, we consider the validity of the almost universally adopted nearest-neighbor model for the kinetic analysis of impurity diffusion in fcc crystals. A crucial question is whether the binding energy for vacancy-impurity pair beyond the nearest-neighbor distance is negligible compared to that for a nearest-neighbor pair. To settle this point, further detailed calculation of the binding energy would be required. However, judging from the generally small values obtained here for the binding energy of nearest-neighbor pair, it seems possible that some more distant pairs can have comparable stability. If this were the case, a kinetic model incorporating more distant jumps than those shown in Fig. 5 would be required. For Al, values of the interatomic potential from the second to the fifth neighbor positions are comparable in magnitude and therefore any extension beyond the nearest-neighbor model would be very complicated.

ACKNOWLEDGEMENT

One of us (R.B) wishes to acknowledge the support provided by the United States Atomic Energy Commission under contract AT (11-1)-3158.

Additional support was received from the Advanced Research Projects Agency and the National Science Foundation through the Materials Science Center at Cornell University.

APPENDIX

In this appendix, it is shown that the volume dependent part of the crystal energy may be neglected in binding energy and migration energy calculations.

Consider the migration of an isolated vacancy. The migration energy may be expressed as

$$E_m = \phi_{sp}(N, \Omega_{sp}) - \phi_v(N, \Omega_v), \quad (A.1)$$

the difference in crystal energies for the saddle point and simple vacancy configurations. N is the number of atoms and Ω the total volume of the relaxed crystal. Since the vacancy formation volume differs in general from the self diffusion activation volume, $\Omega_{sp} \neq \Omega_v$. Subtracting and adding the energy of a perfect crystal, $\phi(N, \Omega)$, to equation (A.1) one obtains

$$E_m = [\phi_{sp}(N, \Omega_{sp}) - \phi(N, \Omega)] - [\phi_v(N, \Omega_v) - \phi(N, \Omega)] \equiv E_f^{sp} - E_f^v \quad (A.2)$$

The term within the second pair of brackets is simply the vacancy formation energy. In earlier work¹⁵, it was shown that this may be expressed in the form

$$E_f^v = E_c^v + E_R^v - E_d - E_s \quad (A.3)$$

where the first two terms on the right hand side are respectively the

"configuration" and "relaxation" energies, E_d is the change in pairwise interaction energy associated with a uniform expansion of the crystal by one atomic volume and E_s is the pairwise interaction energy of a surface atom. In deriving Eq. (A.3), the perfect crystal is taken to be at equilibrium. An expression similar to A.3 may be derived for E_f^{sp} :

$$E_f^{sp} = E_c^{sp} + E_R^{sp} - E_d - E_s \quad (A.4)$$

Substituting equation (A.4) and (A.3) into (A.2) one obtains

$$E_m = E_m^c + E_m^R$$

where

$$E_m^c = E_c^{sp} - E_c^v,$$

$$E_m^R = E_R^{sp} - E_R^v$$

Thus the migration energy is expressed in terms of configuration and relaxation contribution, both of which are determined by the pairwise interactions.

The above discussion is concerned with the migration of an isolated vacancy. Similar derivations may be carried out for the impurity-vacancy binding energy and migration energies in the presence of an impurity. One obtains, for example,

$$E_b = E_b^c + E_b^R$$

a relation used in section IV.

REFERENCES

1. See for example: Phase Stability in Metals and Alloys, edited by P. S. Rudman et al. (McGraw-Hill Book Co., New York, 1967).
2. V. K. Tewary, A.E.R.E. Harwell Report T.P. 548 (1973); see also R. Benedek and P. S. Ho, J. Phys. F: Metal Phys. 3, 1285 (1973).
3. See the recent review by R. W. Balluffi and P. S. Ho, in ASM Seminar for Diffusion, edited by H. I. Aaronson (Am. Society of Metals, Ohio, 1974).
4. N. L. Peterson and S. J. Rothman, Phys. Rev. B1, 3264 (1970).
5. S. M. Edelglar and M. Ohring, Trans. AIME 245, 186 (1969).
6. V. Heine and D. Weaire in Solid State Physics, Vol. 24, edited by H. Ehrenreich et al. (Academic Press, 1970).
7. See for example: Pseudopotentials in the Theory of Metals, by W. A. Harrison (Benjamin Inc., New York, 1966).
8. N. W. Ashcroft, in Interatomic Potentials and Simulation of Lattice Defects, edited by P. C. Gehlen et al. (Plenum Press, New York, 1972) pp. 91 to 110.
9. R. W. Shaw, Jr., Phys. Rev. B5, 4742. (1972).
10. P. S. Ho, Phys. Rev. B3, 4035 (1971); *ibid.* B7, 3550 (1973).
11. V. Heine and I. Abarenkov, Phil. Mag. 9, 451 (1964).
12. D. Lazarus, Phys. Rev. 93, 973 (1954) and R. A. Swalin, Acta Met. 5, 443 (1957).
13. M. S. Duesbery and R. Taylor, Phys. Rev. B7, 2870 (1973).
14. D. J. W. Geldart and R. Taylor, Can. J. Phys. 48, 167 (1970).
15. R. Benedek and P. S. Ho, J. Phys. F, to be published.
16. W. M. Shyu, J. H. Wehling, M. R. Cordes and G. D. Gaspari, Phys. Rev. B4, 1802 (1971).
17. R. E. Howard and J. R. Manning, Phys. Rev. 154, 561 (1967).
18. A. D. LeClaire, Phil. Mag. 7, 141 (1962).
19. J. Burke and A. D. King, Phil. Mag. 21, 7 (1970).

20. D. R. Beaman, R. W. Balluffi and R. S. Simmons, Phys. Rev. 137A, 917 (1965).
21. B. T. A. McKee, A. T. Stewart and M. J. Stott, Conf. on Point Defects and Their Aggregates in Metals, University of Sussex, England (1972).
22. L. Pauling, The Nature of the Chemical Bond, Cornell University Press, Ithaca, New York (1940).

TABLE I
THEORETICAL BINDING ENERGY FOR IMPURITY-VACANCY
PAIR IN ALUMINUM

(All units in eV)

IMPURITY	$\phi_{AB}(r_1)$	E_b^c	E_R^s	E_R^{vs}	E_b^R	E_b
$Z_b = 2$ $R_m^b = R_m^a$	.069	-.034	-.008	-.104	.012	-.022
$Z_b = 4$ $R_m^b = R_m^a$	.138	.035	.007	-.075	-.016	.019
$Z_b = 3$ $R_m^b = .9R_m^a$	.099	-.004	-.002	-.091	.005	.001
$Z_b = 3$ $R_m^b = 1.1 R_m^a$	.115	.012	-.005	-.075	-.014	-.002

NOTE: $\phi_{AA}(r_1) = .103$; $E_R^v = -.084$

TABLE II
THEORETICAL ΔE FOR IMPURITY MIGRATION IN ALUMINUM

(All units in eV)

IMPURITY	$E_C^S (\omega_2)$	ΔE_C	$E_R^S (\omega_2)$	ΔE_R	ΔE
$Z_b = 2$ $R_m^b = R_m^a$	1.318	-.276	-.243	.209	-.067
$Z_b = 4$ $R_m^b = R_m^a$	2.637	.276	-.648	-.225	.051
$Z_b = 3$ $R_m^b = .9R_m^a$	1.619	-.306	-.279	.160	-.146
$Z_b = 3$ $R_m^b = 1.1R_m^a$	2.449	.347	-.643	-.220	.127

Note: $E_C^S (\omega_2)$ is the "configuration" energy for the unrelaxed impurity saddle-point. Other parameters needed for calculating ΔE are: 1.977 eV for the configuration energy of the host saddle-point and -.432 eV for $E_R (\omega_0)$.

TABLE III
THEORETICAL ΔQ FOR IMPURITY DIFFUSION IN ALUMINUM
(All units in eV)

IMPURITY	ΔE	E_b	ΔQ
$Z_b = 2$ $R_m^b = R_m^a$	-.067	-.022	-.045
$Z_b = 4$ $R_m^b = R_m^a$	.051	.019	.032
$Z_b = 3$ $R_m^b = .9R_m^a$	-.146	.001	-.145
$Z_b = 3$ $R_m^b = 1.1 R_m^a$	.127	-.002	.125

Figure Captions

- Figure 1: Interatomic potentials for homovalent impurities in Al. The potential scale has been expanded tenfold for $r > 9$ a.u. to show the oscillations in the potential. The positions of the first five neighbors are also indicated. The parameters used in the host potential are $R_m^a = .71 \text{ \AA}$ and $\alpha_a = .42$.
- Figure 2: Schematic illustration of splitting ϕ into ϕ^+ and $-\delta\phi$ for the saddle-point configuration of an impurity ω_2 jump.
- Figure 3: The formation of an impurity-vacancy pair in (b) is accomplished by bringing together the isolated vacancy and impurity in (a).
- Figure 4: (111) projection of displacement field for vacancy-impurity pair in Al. This impurity has $Z_b = 4$ but the same R_m as Al.
- Figure 5: Various atomic jump frequencies entering kinetic analysis of impurity diffusion in the Howard-Manning¹⁷ model.
- Figure 6: Valence of R_m for various elements obtained by Shaw⁹ for the optimized model potential vs. Pauling ionic radii,²² along with diffusion data for impurity in Al. The references for these data are given in reference 3.

Figure 1

Figure 2

(a)

(b)

Figure 3

(III) PROJECTION OF DISPLACEMENT FIELD FOR
VACANCY-IMPURITY PAIR IN Al

Figure 5

SOLUTE	Z_s	E_b (eV)	ΔQ (eV)
Cu	1	.00	.14
Ag	1	.05	-.05
Zn	2	.02	-.006
Cd	2	--	.03
Ga	3	-.04	.01
In	3	--	.01

Figure 6