FINAL REPORT

Contract AT(11-1)-125

MASTER

between

The United States Atomic Energy Commission

and

Purdue University

Submitted by

J. W. MacKay

Principal Investigator

June 14, 1974

NOTICE

This report was prepared as an account of work sponsored by the United States Government. Neither the United States nor the United States Atomic Energy Commission, nor any of their employees, nor any of their contractors, subcontractors, or their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness or usefulness of any information, apparatus, product or process disclosed, or represents that its use would not infringe privately owned rights.

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency Thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

DISCLAIMER

Portions of this document may be illegible in electronic image products. Images are produced from the best available original document.

INTRODUCTION

This final report spans the terms of three principal investigators. The research program was initiated by K. Lark-Horovitz in 1950 and continued under his direction until his death in 1958. H. M. James was principal investigator from 1958 to 1965 when he was succeeded by J. W. MacKay.

There is some difficulty in clearly distinguishing work supported by this contract from work supported by a Signal Corps contract during the period 1950 to 1958. However, all work referred to in this report received at least partial support from AEC contract AT(11-1)-125.

At its inception, the research program encompassed studies of the effects of radiations on the mechanical and electrical properties of both metals and semiconductors. Within a few years, a special interest in semiconductors led to focussing the effort on the effects of electron irradiations on semiconductors only. The materials that received intensive investigation are: Ge, Si, InSb and InAs.

PRINCIPAL ACCOMPLISHMENTS

Defect Energy Levels

Early work (1 - 4) was devoted to characterising the effects of electron irradiation on the electrical properties of germanium in the temperature range 80K to 300K. Hall effect and conductivity measurements were utilized to determine the positions in the forbidden energy gap of the electronic states associated with defects.

Later, similar measurements were made on Si (7) and on InSb and InAs (8,9). This information tells little about the nature of specific defects but was very useful data for use in predicting the effects of irradiation on devices fabricated from these materials. Additional information on defect energy levels in Ge was obtained through a study of photoconductivity (6).

Low Temperature Damage and Annealing in Ge

We were among the first to study radiation damage in semiconductors at liquid helium temperature (10,11). Beginning with degenerate material, we established that there are two annealing stages in the electrical properties of n-type Ge at low temperature. One stage is centered at 35K, the other at 65K. In contrast, we found that p-type Ge is nearly immune to damage by 1 MeV electrons when the specimen is irradiated at liquid helium temperature.

In these same experiments, we discovered that annealing of damage is produced when a damaged specimen is irradiated by electrons with energy below the threshold for damage.

Based on these results, we proposed that the motion, and recombination, of vacancies and interstitials is strongly affected by the charge state of the defects. This idea proved to be very fruitful and led to subsequent investigations by ourselves, and by others, of annealing induced by light and by carrier injection. A detailed model was developed (13) in which the dominant defects were postulated to be close pairs of vacancy and interstitial. The model was successful in describing many of the facets of defect production and annealing. However, the model was later abandoned when it became clear that long range defect motion occurs during irradiation and annealing.

Stored Energy Release in Ge

In order to determine whether vacancy-interstitial annihilation occurs in the low temperature annealing stages in n-type Ge, and to verify that no similar annealing occurs in p-type, we undertook the measurement of stored energy release as an irradiated specimen is warmed from 4.2K to 100K (21). Our measurements demonstrated clearly that interstitial-vacancy annihilation was indeed the annealing mechanism in n-type Ge. No stored energy release was observed in p-type Ge, confirming the results of our earlier measurements on electrical properties.

High Field Pulsed Conductivity Measurements

In order to extend the measurements of electrical properties at liquid helium temperature to lightly doped Ge samples, we employed high-field pulsed conductivity (hot carrier) measurements. These studies (15, 18) showed that defects are introduced into lightly doped n-type Ge at the same rate as in degenerate material. However, no 35K annealing is observed. We were also able to study how the annealing is affected by irradiation energy. Higher energy bombardment introduces a larger fraction of stable defects.

Hot carrier measurements were also applied to the study of photo-induced annealing at 4.2K (25) as well as to the effect of different group V impurities on the 65K annealing stage (30, 34). The latter work provides evidence that long-range defect migration occurs during radiation and annealing at low temperatures.

X-Ray Lattice Parameter Measurements

In a cooperative effort with a group at Dow Corning (23)

combining mass spectrometry, infrared absorption and X-ray lattice parameter measurements, we established that high purity Si such as 'Lopex' and 'Perfex' contain substitutional C impurities in excess of 10^{16} cm^{-3} . Carbon produces a change in lattice parameter $\Delta a/a = -6.5 \times 10^{-24}$ per carbon atom per cm^3 .

In further work of our own (27) the effect of various group III and V impurities on the lattice parameter of Si was investigated. All impurities examined produced a decrease in lattice parameter. Irradiation at room temperature produced an increase in lattice parameter corresponding to relief of about 50% of the strain introduced by the initial doping impurities. This was true for C as well as group III and V impurities.

Change in Length Measurements

In work supported by another agency, colleagues began measurement of length change in Ge under electron irradiation. They found that 'pure' Ge expands but heavily doped n-type Ge contracts when irradiated at liquid helium temperature. P-type Ge is unaffected by irradiation. They interpreted the expansion of 'pure' Ge to be due to introduction of neutral defects. The contraction of degenerate n-type material was attributed to an effect on the volume when electrons are removed from the conduction band, which is of opposite sign and greater magnitude than the expansion produced by a neutral defect. We continued this investigation and were able to directly measure the electronic volume effect as electrons are transferred from defect states to the conduction band.

Temperature Dependence of Damage and Radiation Annealing in Si

Our early work on degenerate Si irradiated at liquid helium temperature (7) established that the number of defects introduced per incident electron is large for p-type while n-type is essentially immune to damage (Opposite to the behavior for Ge). In more recent work (29) we observed that the rate of defect production in n-type Si rises sharply between 60K and 120K. Most surprising, we found that damage introduced by irradiation at temperatures above 60K is removed if the radiation is continued at a temperature below 60K.

We have studied this radiation annealing further by using infrared absorption measurements to monitor which defects are affected by the radiation annealing at low temperature (31). The A-center is unaffected, but the di-vacancy disappears under radiation annealing. We were unable to monitor the E-center by optical measurements.

CONCLUSION

In addition to the scientific accomplishments referred to in this report, contract AT(11-1)-125 provided support for the training of twenty PhD scientists. While this educational function is no longer a major concern of governmental agencies, we regard the training of these people as one of the important accomplishments under this contract.

J. W. MacKay
Principal Investigator
June 14, 1974

PUBLICATIONS

1. K. Lark-Horovitz, in Semiconducting Materials (Butterworth Scientific Publications, London 1951)
"Nucleon Bombarded Semiconductors"
2. H. Y. Fan and K. Lark-Horovitz, in Defects in Crystalline Solids
Report of the 1954 Bristol Conference (Phys. Soc. London 1954)
"Fast Particle Irradiation of Germanium Semiconductors"
3. K. Lark-Horovitz, in The Present State of Physics (American Association for the Advancement of Science, 1954)
"The New Electronics"
4. H. Y. Fan and K. Lark-Horovitz, in Effects of Radiation on Materials (Reinhold Publishing Corp. New York, 1958)
"Irradiation Effects in Semiconductors"
5. F. Stoekmann, E. E. Klontz, J. W. MacKay, H. Y. Fan and K. Lark-Horovitz, Zeit. fur Physic 153, 331 (1958)
"Photoconductivity of Ge Irradiated with Fast Electrons"
6. W. E. Spear, Phys. Rev. 112, 362 (1958)
"Surface Effects in Electron Irradiated Ge at 80K"
7. D. E. Hill, Phys. Rev. 114, 1414 (1959)
"Electron Bombardment of Silicon"
8. L. W. Aukerman, Phys. Rev. 115, 1125 (1959)
"Electron Irradiation of InSb"
9. L. W. Aukerman, Phys. Rev. 115, 1133 (1959)
"Electron Irradiation of InAs"
10. J. W. MacKay, E. E. Klontz and G. W. Gobeli, Phys. Rev. Letters 2, 146 (1959)
"Thermal and Radiation Annealing in Ge"
11. J. W. MacKay and E. E. Klontz, J. Appl. Phys. 30, 1269 (1959)
"Low Temperature Annealing Studies in Ge"
12. E. E. Klontz and J. W. MacKay, J. Phys. Soc. Japan 18, Suppl. III, 1216 (1963)
13. J. W. MacKay and E. E. Klontz, in Radiation Damage in Solids, Vol. III, 27 (International Atomic Energy Agency, Vienna, 1963)
"The Role of Carriers in the Displacement Process in Ge"
14. J. W. MacKay and E. E. Klontz, in Radiation Damage in Semiconductors, P. Baruch Editor (Dunod, Paris 1965)
"Low Temperature Irradiation of Semiconductors and Ionization Effects"

15. J. W. MacKay and T. A. Callcott, in Radiation Damage in Semiconductors, P. Baruch, Editor (Dunod, Paris 1965)
"Application of Hot Carrier Techniques to the Study of Radiation Damage in Ge"
16. E. E. Klontz, J. W. MacKay and T. M. Flanagan, in Radiation Damage in Semiconductors, P. Baruch, Editor (Dunod, Paris, 1965)
"Electron Irradiation of p-Type Ge at 0° C"
17. J. E. Whitehouse, Phys. Rev. 143, 520 (1966)
"Electron Irradiation of P-Type Ge at 4.2K"
18. T. A. Callcott and J. W. MacKay, Phys. Rev. 161, 698 (1967)
"Irradiation Damage in n-Type Ge at 4.2K"
19. D. L. Trueblood, Phys. Rev. 161, 828 (1967)
"Electron Paramagnetic Resonance in Electron Irradiated Ge"
20. Y. Chen and J. W. MacKay, Phys. Rev. 167, 745 (1968)
"Subthreshold Electron Damage in n-Type Ge"
21. M. P. Singh and J. W. MacKay, Phys. Rev. 175, 985 (1968)
"Stored Energy Release in Electron Irradiated Ge"
22. T. M. Flanagan and E. E. Klontz, Phys. Rev. 167, 789 (1968)
"Bombardment Produced Defects in p-Type Ge at Low Temperatures"
23. J. A. Baker, T. N. Tucker, N. E. Moyer and R. C. Buschert, J. Appl. Phys. 39, 4365 (1968)
"Effect of Carbon on the Lattice Parameter of Si"
24. J. W. MacKay and E. E. Klontz, in Radiation Effects in Semiconductors, F. Vook, Editor (Plenum Press, New York, 1968)
"Effects of Defect Charge State on Radiation Damage in Semiconductors"
25. Itsu Arimura and J. W. MacKay, in Radiation Effects in Semiconductors, F. Vook, Editor (Plenum Press, New York, 1968)
"Photo-induced Annealing in n-Type Ge"
26. E. E. Klontz and L. Sivo, in Radiation Effects in Semiconductors, F. Vook, Editor (Plenum Press, New York, 1968)
"Radiation Annealing in Degenerate n-Type Si"
27. N. E. Moyer and R. C. Buschert, in Radiation Effects in Semiconductors, F. Vook Editor (Plenum Press, New York, 1968)
"X-Ray Lattice Parameter Studies of Electron Irradiated Si"
28. Y. Chen and J. W. MacKay, Phil. Mag. 19, 357 (1969)
"Orientation and Temperature Dependence of Electron Damage in n-Type Ge"
29. L. L. Sivo and E. E. Klontz, Phys. Rev. 178, 1264 (1969)
"Studies of Radiation Damage in Degenerate Si Irradiated at Low Temperatures"

30. J. M. Meese and J. W. MacKay, Radiation Effects 8, 161 (1971)
"Impurity Dependence of the Low Temperature Annealing in
n-Type Ge"
31. J. W. MacKay and E. E. Klontz, Radiation Effects 9, 27 (1971)
"Review of Radiation Effects in Ge"
32. R. A. Matula and E. E. Klontz, Radiation Effects 9, 37 (1971)
"Defects Induced by Electron Irradiation of p-Type Ge"
33. J. E. Whitehouse, J. Phys. Chem. Solids 32, 677 (1971)
"Defect Production in n-Type Ge by Electron Irradiation
at Low Temperature"
34. J. M. Meese, Phys. Rev. B 9, 4373 (1974)
"Low-Temperature Recovery of Irradiation Defects in n-Type Ge"

PhD THESES

- E. E. Klontz: Production of Lattice Defects by Electron Bombardment (June 1952)
- N. Pearlman: Low Temperature Atomic Heat of Silicon, Germanium and Silver (June 1952)
- A. M. Liebschutz: Diffuse Scattering as a Function of Nucleon Irradiation (August 1953)
- L. Aukerman: Electron Irradiation of Indium Antimonide and Indium Arsenide (February 1958)
- D. E. Hill: Electron Bombardment of Silicon (January 1959)
- R. R. Pepper: Electron Irradiation of Germanium (August 1959)
- J. M. Kortright: Dependence of Irradiation Damage in Germanium on Intensity of Irradiation (June 1963)
- M. P. Singh: Stored Energy Release in Electron Irradiated Germanium (August 1964)
- T. A. Callcott: High Field Conductivity Studies of n-Type Germanium Irradiated at 4.2 K (June 1965)
- Y. Chen: Sub-Threshold and Above-Threshold Damage in n-Germanium (January 1966)
- J. A. Naber: Pulse and Irradiation Annealing of n-Type Germanium (January 1966)
- D. L. Trueblood: EPR in Electron Irradiated Germanium (January 1966)

T. M. Flanagan: Fast Electron Damage and Annealing in p-Type Germanium (June 1966)

L.L. Sivo: Radiation Damage Studies in Degenerate Silicon Irradiated at Low Temperatures (June)1967)

I. Arimura: Photo-Induced Annealing and Photoconductivity in Low Temperature Irradiated Germanium (August 1967)

N. E. Moyer: An x-Ray Study of the Lattice Parameter of Silicon (June 1968)

J. M. Meese: Impurity Dependence of the Thermal and Irradiation Annealing of the 65 K Stage in Irradiated n-Type Germanium (June 1970)

J. K. Gotwals: Dilation of Electron Irradiated Germanium (June 1971)

G. M. Cohen: Infrared Studies of Radiation Damage in n-Type Silicon (December 1972)

R. A. Matula: Defects Induced by Electron Irradiation of p-Type Germanium at Low Temperature (August 1973)