ARGONNE NATIONAL LABORATORY
P. O. Box 299
Lemont, Illinois

QUARTERLY REPORT
APRIL, MAY, AND JUNE 1957

METALLURGY DIVISION

Frank G. Foote, Director
James F. Schumar, Associate Director
Haim H. Chiswik, Associate Director

July 1958

Previous Quarterly Reports.

ANL-5717 January, February, March 1957
ANL-5709 October, November, December 1956
ANL-5643 July, August, September 1956

Operated by The University of Chicago
under
Contract W-31-109-eng-38

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency Thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

DISCLAIMER

Portions of this document may be illegible in electronic image products. Images are produced from the best available original document.

TABLE OF CONTENTS

	<u>Page</u>
ABSTRACT	5
I. ADVANCED WATER REACTOR PROGRAM - ACTIVITY 4102	
1. Development of Ceramic-Type Fuel Elements.	9
a. Thoria-Urania Ceramic Fuel Bodies.	9
b. Extended Irradiation of Borax-IV Fuel	10
II. FAST POWER BREEDER REACTOR PROGRAM- ACTIVITY 4104	
1. Manufacture of Rod for Fuel and Blanket Elements for EBR-I, Mark III.	14
III. ADVANCED ENGINEERING AND DEVELOPMENT - ACTIVITY 4530/4540/4580	
1. Effects of Irradiation Upon $\text{ThO}_2\text{-UO}_2$	23
2. Developments in Nondestructive Testing	23
a. Ultrasonic Fluoroscopy Unit	23
b. Ultrasonic Thin-Plate Techniques	25
c. Clad-Thickness Measurements	25
d. Development of Eddy Current Methods	25
3. Corrosion.	26
a. Corrosion-Resistant Uranium Alloys	26
b. Corrosion-Resistant Aluminum Alloys	27
4. Fast Reactor Safety	29
a. Graphite-Urania Fuel Elements for the TREAT Reactor	29
IV. PRODUCTION, TREATMENT, AND PROPERTIES OF MATERIALS - ACTIVITY 5410	
1. Elastic Constants of Alpha-Uranium Single Crystals	31
2. Plastic Deformation Mechanisms in Alpha-Uranium Single Crystals	35

TABLE OF CONTENTS

	<u>Page</u>
IV. PRODUCTION, TREATMENT, AND PROPERTIES OF MATERIALS (Continued)	
3. Thermal Expansion of Alpha-Uranium Single Crystals	37
4. Recrystallization of Heavily Cold-Rolled Uranium Sheet	40
5. Self-Diffusion in Uranium	44
6. Uranium Alloys	50
a. The Uranium-Carbon System.	50
b. Uranium-Molybdenum and Uranium-Ruthenium Systems.	53
c. Uranium-Molybdenum-Ruthenium System	53
d. Properties of Uranium-Fissium Alloys	53
7. Basic Corrosion	53
a. Aqueous Corrosion of Aluminum	53
b. Zirconium Corrosion Mechanism.	55
8. Sintering of Ceramic Materials	56
V. ALLOY THEORY AND THE NATURE OF SOLIDS - ACTIVITY 5420	
1. Occurrence and Magnetic Behavior of Cr_3O -Type and Sigma Phases	59
2. The Hexagonal Phase Found in Certain Zirconium and Titanium Alloys.	59

METALLURGY DIVISION REPORTS AND PAPERS PUBLISHED
DURING THE QUARTERLY PERIOD
APRIL - JUNE 1957

- M. H. Mueller and H. W. Knott, "Effect of Rolling Temperature on the Preferred Orientation in Rolled Uranium Rods," ANL-5329 (March 1957).
- J. E. Draley and W. E. Ruther, "Experiments in Corrosion Mechanism: Aluminum at High Temperatures," ANL-5658 (April 1957).
- W. E. Ruther and W. B. Seefeldt, "Aqueous Corrosion of Uranium and Uranium-6 w/o Zirconium Alloy," ANL-5672 (January 1957).
- F. L. Yaggee, "The Fabrication of Certain Jacketed Uranium Helices," ANL-5690 (May 1957).
- Karl F. Smith, "The Thermal Conductivity of Uranium," ANL-5700, Part A (April 1957).
- Karl F. Smith, "The Electrical Conductivity of Uranium," ANL-5700, Part B (April 1957).
- W. J. McGonnagle, S. McLain, E. C. Wood, "Applications of Nondestructive Testing to Fuel Elements for Nuclear Reactors," Nondestructive Testing 15 (2) 86-90 (March-April 1957).
- J. E. Draley, W. E. Ruther, "Some Unusual Effects of Hydrogen in Corrosion Reactions," J. Electrochem. Soc. 104 329-333 (June 1957).

QUARTERLY REPORT
APRIL, MAY, AND JUNE 1957
METALLURGY DIVISION

ABSTRACT

Advanced Water Reactor Program - Activity 4102

Ceramic Fuels: Samples of 90 w/o ThO_2 -10 w/o UO_2 are in preparation to study the effect of pore structure and density on irradiation stability.

The following reaction couples have been made and studied at 600° and 800°C for 60 days:

1. ThO_2 - UO_2 vs. Zircaloy-2
2. ThO_2 - UO_2 vs. stainless steel
3. ThO_2 - UO_2 vs. lead
4. Lead vs. Zircaloy-2
5. Lead vs. stainless steel
6. Graphite vs. Zircaloy-2
7. Graphite vs. ThO_2 - UO_2

Results: no reactions at 600°C, lead appeared to react with Zircaloy-2 at 800°C; no other reactions at 800°C.

Tests of firing shrinkage, thermal expansion and transverse strength are in preparation on 90 w/o ThO_2 -10 w/o UO_2 and 80 w/o ThO_2 -20 w/o UO_2 compositions.

Extended irradiation testing of prototype BORAX-IV fuel plates has been started in MTR. It is planned to continue the test to a state of complete burnup of U^{235} and beyond in some cases to utilize some of the U^{233} provided by conversion of thorium.

Fast Power Breeder Reactor Program - Activity 4104

EBR-I, Mark III. Manufacture of the third core for EBR-I is proceeding. This core will replace the core which was damaged by the partial meltdown in November, 1955. The replacement core is fueled by U-2 w/o Zr alloy, coextrusion bonded to Zircaloy-2. Design of the loading is such as to prevent lateral movement of the fuel elements. Approximately one-third of the billets for the blanket slugs and four-fifths of those for the fuel slugs have been cast and subsequent operations are progressing accordingly.

General Reactor Development - Activities 4530, 4540 and 4580

Irradiation of Thoria-Urania: Tests performed in the BORAX-IV reactor on ThO_2 - UO_2 pellets of three different UO_2 compositions, lead bonded to Al-1 w/o Ni tube sheets, showed considerable fracturing, with some apparent dependence on UO_2 content. Previous tests of this type have not shown such dependence; also, fracturing has been noted in an unirradiated piece. Some of these failures are thereby indicated to have arisen from fabrication and handling procedures prior to irradiation.

Nondestructive Testing: A system for a scanning unit employing a mercury jet commutator with 60 segments has been successfully used in the development of an ultrasonic fluoroscopy unit.

A total of 89 cylindrical uranium castings to be used for the EBR-I, Mark III core have been inspected for shrink and porosity. Eddy current methods are being developed for use in checking final welds of these rods.

Preliminary experiments indicate the feasibility of using beta-ray back scattering for measuring the cladding thickness of ALPR and Argonaut-type fuel plates.

Corrosion: Preliminary tests of uranium-1, 2, and 5 w/o ruthenium alloys fail to show marked improvement over unalloyed uranium. The tests are to be extended to specimens from improved melting and heat treating techniques.

Tests of phosphoric acid inhibitors on M388 aluminum alloy indicate that additional phosphate above that present in phosphoric acid is detrimental to the corrosion rate; both the pH and the anion appear to be important to a low rate.

A new corrosion loop has been started, using distilled water at 260°C to detect velocity effects on M388 aluminum alloy corrosion. Samples in 22 feet/second water have been shown to exhibit an increase in corrosion rate after eleven days, in contrast to samples in 2 feet/second water, which showed no break in rate.

A metal thickness gauge, based on the eddy current principle, has been constructed and used for measuring the amount of aluminum corroded off thin sheets.

Fast Reactor Safety: After several unsuccessful attempts to compact graphite-1 w/o urania for TREAT fuel elements, samples of satisfactory density have now been made, using a binder of 7 w/o phenol-formaldehyde.

Production, Treatment, and Properties of Materials - Activity 5410

Uranium: After the determination of six elastic constants of alpha-uranium single crystals reported in ANL-5717, only the three shear constants remain undetermined. Single crystals are being prepared with axes at specified orientations with respect to the orthogonal directions for the purpose of measuring these three remaining constants.

Equipment has been constructed for high-temperature deformation studies of alpha-uranium single crystals. Using this equipment, a slip band was produced in compression at 600°C in a small single crystal. The slip plane thus produced was about 8° from the (001) plane pole and the slip direction was within 10° from the [100]. The slight deviation noted from the (001) plane is probably accounted for by the lack of free (001) planes passing through the crystal; because of its small size all of these planes terminated on one or the other of the compression platens.

The thermal expansion characteristics of two single uranium crystals in the [010] direction were determined over a temperature range of 23° to 650°C using a recording quartz differential dilatometer and heating and cooling rates of approximately 4°C per minute. The contraction curves fell slightly below the curve obtained from X-ray lattice parameter measurements. The contractions of the two sample crystals to 600°C were 47.11 and 47.87 $\times 10^{-4}$ inch per inch; from X-ray data the corresponding value was 44.06 $\times 10^{-4}$ inch per inch.

The investigation of the extent of recrystallization of alpha uranium which is accompanied by no texture change has continued. Thermal expansion tests on specimens annealed at 400°C indicate no texture change up to 80% recrystallization, but with rapid change thereafter. However, annealing at certain lower temperatures for longer times enables the retention of the same texture to 98% recrystallization. This is a rather surprising result and will be examined further.

A barrier layer of UO_2 has been shown to be present in cathodic sputtering of coatings of zirconium or uranium onto uranium. The presence of such a layer is believed to be responsible for failure of past attempts to detect any self-diffusion of uranium by techniques of sputtering. The purity of the gas used for the sputtering is being rechecked, and modifications in the apparatus are being made to minimize chances for oxidation.

Uranium Alloys: Using high-purity uranium, the following equilibrium transformation temperatures have been measured for uranium-carbon alloys:

alpha-beta	664.9°C
beta-gamma	771.6°C

In comparison with previously reported values for unalloyed high-purity uranium, these results indicate that both the $\alpha \longrightarrow \beta$ and $\beta \longrightarrow \gamma$ transformations in the U-C system are eutectoidal.

The transformation temperature of beta to alpha uranium has been shown to be depressed to $628^\circ \pm 3^\circ\text{C}$ by additions of molybdenum. This transformation is depressed only to $640^\circ \pm 5^\circ\text{C}$ by additions of ruthenium.

The uranium-rich corner of the uranium-molybdenum-ruthenium system has been examined during the past quarter. The gamma phase was retained to room temperature in all alloys examined.

Apparatus for measurement of thermal conductivity of uranium-fissium alloys is under construction and specimens are being fabricated.

Corrosion: Preliminary results of long-term corrosion tests (over 900 days) of 1100 aluminum reported last quarter have been confirmed. Corrosion proceeded at a continuously decreasing rate at 70°C in distilled water and in potassium sulfate solution.

The electrical resistance of oxide films on Zr-0.05/0.50 w/o Ti alloys has been measured to be 10^{13} to 10^{14} ohm-centimeters, depending on temperature, strength of the electrical field, and the environment, but independent of polarity.

Basic Ceramics: Sintering experiments have been performed on single crystal synthetic sapphire spheres in contact with plates of the same material. After sintering at 1800°C in hydrogen, measurement of the necks formed by breaking off the spheres from the plates indicates a volume diffusion mechanism to be operative in the sintering process.

Alloy Theory and the Nature of Solids - Activity 5420

Ti₂Ni-Type Phases: The survey of binary transition metal systems for Cr₃O-type structures has resulted in the discovery of a family of phases, previously unreported, that are isostructural with Ti₂Ni. Preliminary evidence has been obtained that this phase is also stable in certain of the systems of zirconium and titanium with the same element, although many of these do not appear to adhere to the A₂B stoichiometry. Work is now in progress to determine the composition ranges of stability and the lattice parameters for these isomorphs.

The delta phase in the uranium-zirconium binary system has been determined to have hexagonal symmetry with three atoms per unit cell instead of large size cubic as had been indicated by earlier work. The structure appears to be at least partially ordered. It is planned to investigate by neutron diffraction methods a similar intermetallic compound system - the omega phase formed in titanium-vanadium alloys.

I. ADVANCED WATER REACTOR PROGRAM - ACTIVITY 4102.

1. Development of Ceramic-Type Fuel Elementsa. Thoria-Urania Ceramic Fuel Bodies
(J. H. Handwerk, R. C. Lied, P. D. Shalek)

The effect of pore structure and density on the ability of ThO_2 - UO_2 compositions to withstand irradiation is being studied. Samples with varying amounts of porosity (both open and closed voids) will be made from a 90 w/o ThO_2 -10 w/o UO_2 (added as U_3O_8) body. Preliminary work in the preparation of the 1/4" diameter by 1/2" long samples has shown that casting techniques are impractical. Samples containing varying amounts of organic material (Table I) have been prepared by dry pressing. The porosity and pore structure of these samples will be studied after they are fired.

TABLE I

Pellets of Varying Porosities

90 w/o ThO_2 -10 w/o UO_2 with 0.5 w/o CaF_2 Added					
Batch No.*	Carbowax (w/o)	Grain** (v/o)	Grain Size** (mesh)	Forming Pressure. ($\times 10^{-3}$ psi)	No. of Pellets
1-LC	3	-	-	10	3
1-HC	3	-	-	20	2
2-LC	6	-	-	10	2
2-HC	6	-	-	20	3
8-E	3	10	-100 +170	20	2
10-E	3	20	-100 +170	20	2
12-E	6	10	- 60 +100	20	1
13-E	6	20	- 60 +100	10	1
14-E	6	20	- 60 +100	20	1
15-E	6	10	-100 +170	10	3
16-E	6	10	-100 +170	20	2
17-E	6	20	-100 +170	10	1
18-E	6	20	-100 +170	20	3
7-S	3	10	-100 +170	10	1
8-S	3	10	-100 +170	20	2
9-S	3	20	-100 +170	10	1
13-S	6	20	- 60 +100	10	1
16-S	6	10	-100 +170	20	1

*C = Control pellets

E = Ethocel Grain used in pellets

S = Shellac grain used in pellets

**Refers to combustible Ethocel or Shellac grains

Samples to study the possibility of reactions between $\text{ThO}_2\text{-UO}_2$ and Zircaloy-2, $\text{ThO}_2\text{-UO}_2$ and stainless steel, $\text{ThO}_2\text{-UO}_2$ and lead, lead and Zircaloy-2, lead and stainless steel, graphite and Zircaloy-2, and graphite and $\text{ThO}_2\text{-UO}_2$ were encased in Vycor tubes. One set of samples was heated to 600°C and a second set was heated to 800°C for a period of 60 days. After firing, the reaction zones were examined metallographically. No reaction was indicated in the samples heated to 600°C . In the samples heated to 800°C , lead appeared to react with Zircaloy-2. No other reactions were apparent at this temperature. Photomicrographs of samples heated at 800°C are shown in Figures 1 - 4.

Samples of thoria-urania bodies having the compositions 90 w/o ThO_2 -10 w/o UO_2 and 80 w/o ThO_2 -20 w/o UO_2 (added as U_3O_8) have been made in the form of right cylinders, $1/4$ " in diameter, to be used to determine the firing shrinkage, thermal expansions, and transverse strengths.

b. Extended Irradiation of BORAX-IV Fuel (J. H. Kittel)

The present peak heat flux in the $\text{ThO}_2\text{-UO}_2$ -fueled BORAX-IV reactor is about 160,000 BTU/hour-ft², with a maximum central fuel temperature of less than 500°C . Earlier irradiation experiments (ANL-5623, pp. 20-22) have indicated that this fuel material should be capable of higher burnup at higher central temperatures and surface heat flux than is possible in the BORAX-IV core. Accordingly, a series of irradiations have been started in the MTR in which specimens in the form of small, prototype BORAX-IV fuel plates are being irradiated at appreciably higher fuel temperatures and heat fluxes than are feasible in BORAX-IV.

A typical fuel specimen is shown in Figures 5 and 6. It consists of two rows of ThO_2 -6.36 w/o UO_2 pellets, highly enriched, lead-bonded to the Al-1 w/o Ni cladding. The specimens are being irradiated in aluminum holders shown in Figures 7 and 8. These holders provide a $1/16$ " annulus around each plate for coolant flow. The ends of the holders are nested so that a vertical column is properly aligned to preserve coolant flow with minimum disturbance. Several holders can be stacked in a standard X-basket and reactor process water is used as the coolant. It is planned to irradiate part of the specimens until burnup of the U^{235} is essentially complete. Other specimens will be taken to higher burnups by irradiating them to a sufficient extent to utilize U^{233} provided by thorium conversion. Specimens with higher UO_2 contents have also been fabricated to facilitate higher burnups.

Figure 1. Lead and Zircaloy-2 Heated 60 Days at 800°C.

Figure 2. $\text{ThO}_2\text{-UO}_2$ Pellet in Stainless Steel Capsule with a Lead-Filled Annulus Heated at 800°C.

Figure 3. $\text{ThO}_2\text{-UO}_2$ Pellet in Zircaloy-2 Cylinder
Heated at 800°C .

Zircaloy-2
Micro 21801

$\text{ThO}_2\text{-UO}_2$

100-X

Figure 4. $\text{ThO}_2\text{-UO}_2$ Pellet in Contact with Zircaloy-2
Pellet Heated at 800°C .

$\text{ThO}_2\text{-UO}_2$

Zircaloy-2

Micro 21802

100-X

Figure 5. Typical Fuel Specimen for Extended Irradiation of $\text{ThO}_2\text{-UO}_2$.

Macro 21174

1-X

Figure 6. Longitudinal Section of Above Specimen Showing Lead-Bonding Between Ceramic Fuel Pellets and Aluminum Alloy Cladding.

Macro 21175

1-X

Figure 7. Aluminum Holder and Fuel Plate, with End Pin Removed to Permit Partial Withdrawal of Fuel Plate.

Macro 21479

2-X

Figure 8. Two Adjoining Holders Showing How Ends are Nested to Align a Vertical Column and Preserve Coolant Flow with Minimum Disturbance.

Macro 21173

1/2-X

II. FAST POWER BREEDER REACTOR PROGRAM - ACTIVITY 4104

1. Manufacture of Rod for Fuel and Blanket Elements for EBR-I, Mark III (R. E. Macherey, N. J. Carson, Jr., R. L. Salley)

General Methods: The Mark III fuel and blanket loading of the EBR-I has been designed in an attempt to eliminate lateral movement (bowing) of the fuel elements during reactor operation. The fuel element design chosen to accomplish this objective was the clad-ribbed rod shown in Figure 9. The difficulty encountered in the fabrication of a rod with the ribs integral with the cladding led to the adoption of a rod of plain cylindrical cross section upon which ribs in the form of round wire are bonded by spot welding.

As shown in Figure 9, the base rod, cylindrical in cross section, has an U-2 w/o Zr alloy core, 0.364" diameter, surrounded and bonded to Zircaloy-2 cladding, nominally 0.020" thick. Clad rods are being produced by coextrusion of composite billets. Three types of rod are needed for the assembly of the fuel and blanket elements involved in the reactor core loading: (1) fuel rods, (2) fuel blanket rods, and (3) inner blanket rods. Two sizes of billets are used for the extrusion of these three types of rod. Because of the weight limitations imposed by criticality considerations in the handling of highly enriched uranium (93% U^{235}) and by the volume of U-2 w/o Zr alloy which could be produced in the vacuum induction furnaces available, a 5-kg billet core was selected. These billets are proportioned for cores of 2" diameter extrusion billets. In order that the natural uranium fuel blanket rods match the enriched uranium fuel rods as closely as possible in dimensions and physical characteristics, these billet cores are produced by an identical procedure. The weight of cores for the natural uranium blanket rod billets is not restricted by the above limitations but by the extrusion press available for fabrication of the rod. A $2\frac{3}{4}$ " diameter billet was chosen since extrapolation of procedure is within range of the 2" diameter billet upon which development data are available. Since these billets contain cores about double the weight of the 2" billet cores, the number of $2\frac{3}{4}$ " billets required is proportionately reduced. The processing sequence employed in the production of the base rod is as follows:

1. Production of the U-2 w/o Zr core alloy billet cores.
2. Production of Zircaloy-2 cladding and protective jacket components.
3. Assembly and evacuation of extrusion billets.
4. Extrusion of billets into clad rod.
5. Processing of rod for fuel and blanket assemblies.
6. Processing of Zircaloy-2 rod for end plugs and zirconium wire for ribs.
7. Heat treatment and cleaning of fuel and blanket rods.

Figure 9. Design and Dimensions of EBR-I, Mark III Fuel and Blanket Rods.

The procedures involved in the above steps are discussed in the following subsections.

Production of U-2 w/o Zr Alloy Billet Cores: The cores castings of the composite extrusion billets for the blanket rods are poured in multiples from heats in the 190-kg size. Melting, by vacuum induction, is done in graphite crucibles coated in turn with magnesium zirconate, then with thoria. Uranium biscuit and zirconium sponge are charged together and alloyed by solution of the alloying element in molten uranium. The heats are bottom-poured into an eight-cavity solid graphite mold coated with MgOZrO_2 . The mold cavities were nominally $2\frac{1}{2}$ " diameter x 15" deep. Each casting was of sufficient length to yield two billet cores, 7" long.

The cast structure of the alloy, because of the slow cooling rate, was such as to produce a core-to-clad interface which was rough. This led to large variations in cladding thickness and core diameter from point to point very close to each other (high-frequency wave in interface). This roughness was reduced by an isothermal quench from the gamma phase. The castings were heated to 790°C in salt and quenched in lead at 500°C. Quenching into baths at temperatures of 400°C and lower produced cracking in the castings. After heat treatment, the billet core castings were machined to the dimensions shown in Figure 10.

The billet core castings for the enriched uranium fuel and natural uranium fuel blanket rods were cast on a 5-kg scale. The natural uranium blanket billets were made by the same procedure as the enriched to pilot the enriched billet castings, and so that the fuel blanket and fuel rods would be as nearly alike as possible.

Melting of these heats was done in a 6" Vycor tube vacuum induction furnace. High-purity MgO crucibles were used. The charge for these heats were crystal bar zirconium wire and enriched uranium buttons or natural uranium biscuit. The heats were poured into a single-cavity graphite mold washed with a coating of 98% thoria-2% zirconia. Each heat yielded a single billet core casting.

Because of the smaller cross section and less weight of metal, a faster cooling rate developed in this casting than in the larger blanket billet castings. For this reason, the as-cast structure produced a satisfactory core-to-clad interface, eliminating the need for heat treatment. These castings were also machined by turning to the dimensions of the billet cores shown in Figure 11.

Production of Zircaloy-2 Cladding and Jacket Components: Zircaloy-2 was selected as the cladding material for the fuel and blanket rod. The 12" diameter, 1000-pound, double arc-melted ingot was forged to a bar $6\frac{3}{4}$ " in diameter. Forging was done at a nominal temperature of 970°C.

Figure 10. Design and Dimensions of 2-3/4" Diameter Extrusion Billets for Blanket Rods

Figure 11. Design and Dimensions of 2" Diameter Extrusion Billets for Fuel and Fuel Blanket Rods.

The forged bar was shipped to Nuclear Metals, Inc., where two sizes of billets were made for conversion into tubing for cladding of the 2" and 2 $\frac{3}{4}$ " billets. The tube for the 2" billets was extruded at NMI to 1 $\frac{1}{2}$ " I.D. x 2 $\frac{1}{32}$ " O.D. (copper jacket removed) by a double extrusion process. The tube for the 2 $\frac{3}{4}$ " billets was extruded at Revere Copper and Brass Company to 2 $\frac{5}{32}$ " I.D. x 2 $\frac{1}{2}$ " O.D. (copper jacket removed). Copper was utilized as the jacket material in all extrusions.

The copper jackets were stripped by pickling and the cladding cylinders were machined to the dimensions shown in Figures 10 and 11. The cladding cylinders were finally prepared for assembly by pickling in boiling, concentrated nitric acid containing 1/2 to 1% HF.

Stock for the Zircaloy-2 end seals used in the 2" billets was produced by extrusion from copper-jacketed billets into 1 $\frac{3}{4}$ " diameter bar at Revere. Copper jackets were stripped by pickling and the end seals were machined to the dimensions shown in Figure 11. These discs were pickled by the same procedure used for the cladding sleeves.

Cu-10 w/o Ni plugs were used as internal nose plugs and internal cutoffs in both the 2 $\frac{3}{4}$ " and 2" billets. Bar stock of approximate dimensions for both billets was produced by extrusion. Final dimensions of these parts were produced by turning.

Copper was used as a jacket material for both types of billets. The container for the 2" billets was commercial 2" O.D. x 16 gage, seamless, deoxidized copper tubing. The container for the 2 $\frac{3}{4}$ " billets was drawn to the dimensions shown in Figure 10 from 3" O.D. x 16 gage, seamless deoxidized copper tubing. Front end plugs for both types of billet were drawn from 16 gage copper disc. The rear end plugs were machined from 1/4" thick, deoxidized copper plate. These rear end plugs were fitted with 1/4" O.D., seamless copper tubes for the evacuation of the billets. Welding of these was facilitated by the grooves for heat concentration shown in Figures 10 and 11. The container end plugs, copper nickel plugs and cutoffs were prepared for assembly by pickling in nitric acid.

Assembly and Evacuation of Extrusion Billets: After the cladding billet components were prepared, the extrusion billets were assembled and the end plugs sealed by welding. The billets were then connected to an evacuation chamber in groups of 10 and evacuated overnight. The system was operated at an absolute pressure in the 10^{-5} mm range. The following morning the billets were heated by means of resistance-type furnaces to 100°C for partial outgassing. Evacuation tubes were then sealed and the billets packed and shipped to Nuclear Metals, Inc., for extrusion.

Extrusion of Billets into Clad Rods: When the billets are received by Nuclear Metals, evacuation tubes are opened and the billets re-evacuated, outgassed, and resealed. The billets are then heated to 650°C (1200°F) for

extrusion. The billets are extruded through plane circular dies to 0.453" diameter. The reduction in area for the 2" billets is approximately 20:1 and for the $2\frac{3}{4}$ " billets, 40:1. The rods are extruded 0.010" oversize in diameter to provide stock for swaging to diameter. The cladding is extruded 0.002" over the nominal 20-mil finish thickness to provide stock for clean-up of the finish assembled fuel and blanket rods.

Processing of Rod for Fuel and Blanket Assemblies: After extrusion, the coextruded rods are returned to ANL for final processing. The first operation is the stripping of the copper jacket. The fuel and fuel blanket rods are simply immersed in 50% nitric acid and the copper jacket pickled off. This can be done with reasonable safety since these rods are completely clad with Zircaloy-2. Minimum danger of an explosion involving the 2% Zr alloy core and nitric acid is present during pickling of these rods. Since the $2\frac{3}{4}$ " diameter billets used for extrusion of the blanket rod do not have Zircaloy end caps, the ends of the rod are not clad with Zircaloy. The unclad portions of the core alloy must be removed and the ends sealed before removal of copper by pickling. Sealing is done by heliarc welding Zircaloy-2 end caps to the Zircaloy cladding after copper has been removed by turning a short distance from the rod ends.

Following removal of copper, the rods are swaged to a diameter which will reduce the core to the proper diameter of 0.364". Swaging is done on a #4 Torrington swager using long-bladed dies. At this point, the rod diameter is approximately 0.004" over final dimension, to provide stock for cleaning before ribs are welded.

The rods are then subjected to a preliminary heat treatment to stabilize their length before cutting blanket, fuel blanket and fuel rods. For this heat treatment, the rods are sealed in stainless steel pipe which is evacuated to prevent contamination. The pipes containing the rods are then immersed and held 15 minutes in a salt bath at 800°C, then air-cooled. This heat treatment causes the rod to shrink from 6 to 12 mils per inch in length, and the diameter to increase approximately 1 mil. The various types of rod are then cut and machined to appropriate lengths for fuel and blanket rods, and then straightened for assembly.

Zircaloy-2 end caps are then welded and bonded to the blanket rods. Fuel and blanket sections are welded and bonded, and the ends sealed with Zircaloy-2 in the same manner as the blanket rods. The bonding operation involved in sealing the end caps and joining the fuel and fuel blanket sections swells the diameter of the rod in the bonding zone from 1 to 10 mils. If this swelling is over 1 mil, swaging will be employed to reduce the rod to appropriate diameter in this zone.

Processing of Zircaloy-2 Rod for End Plugs and of Zirconium Wire for Ribs: Zircaloy-2 rod, 0.440" diameter, is required for fuel and blanket rod end plugs. This material is produced from forged bar stock, 3" x 9"

cross section. The bar is first flat rolled to $1\frac{1}{2}$ " thickness at 850°C . Bars, $1\frac{1}{2}$ " x $1\frac{1}{2}$ " cross sections, are then cut from this slab and the corners chamfered $3/8$ " at 45° . The chamfering is done to prevent formation of seams in the rod rolling operation which follows. These square bars are then rolled in hand-round passes to 0.475" diameter at 800°C . Final sizing of the rod is done by swaging; rods are straightened on a two-roll Medart rotary straightener.

The 0.056" diameter zirconium wire required for fuel and blanket rod ribs is produced from $1/8$ " thick sheet stock. The sheet is converted to wire by a sequence of shearing, rolling and swaging operations. This strip is cut into $1/8$ " x $1/8$ " strips by shearing. The sheared sides are rolled smooth on flat rolls to reduce shear roughness. The square rods are then swaged to 0.056" diameter wire. The wire is prepared for use by a final pickling operation carried out in 35% HNO_3 -5% HF . No intermediate annealing is required during the fabrication.

Heat Treatment and Cleaning of Fuel Blanket Rods: Heat treatment for irradiation dimensional stability is then performed on the fuel and blanket rods. The isothermal heat treatment has been tentatively established as follows:

15 minutes at 800°C $\longrightarrow$ 1 hour at 690°C $\longrightarrow$ air-cool.

Both the 800°C solution treatment and the 690°C isothermal quench are done by immersing the bare rods in lead at the appropriate temperature. After heat treatment, the rods are straightened and the final diameter established, either by grinding or by a combination of wet abrasive blasting and pickling to remove the 2-mil excess clad present on the rods. In addition, one of these operations will be used to present surfaces free of contamination for the rib welding operation.

If grinding is used, a centerless grinder will be employed. If the blasting-pickling procedure is used, heat treatment contamination will first be removed by wet abrasive blasting using 400 mesh Al_2O_3 ; pickling will be done in a bath containing 35 v/o concentrated HNO_3 and 5 v/o concentrated HF .

The fuel and blanket rods are completed by the attachment of wire ribs by spot welding, milling of the ribs to proper height, and machining the Zircaloy end plugs to appropriate design.

Status of Production: An estimated total of 60 extrusion billets, $2\frac{3}{4}$ " in diameter, is required for the production of blanket rods. The required number of castings to produce these billets has been completed. The rod needed for fuel blanket slugs requires 23 core castings for 2" diameter billets. Twenty of these billets have been cast. An estimated total of 15 enriched billet core castings are required for the fuel slugs, of which 12 have been cast.

All the Zircaloy-2 billet cladding components have been fabricated, and lead and cutoff plugs and copper jacket components have been provided for both sizes of billets. Approximately 50% of the necessary Zircaloy-2 end plug stock has been finished, and 75% of the rib wire is completed.

Fifty-one $2\frac{3}{4}$ " diameter billets have been assembled and shipped to Nuclear Metals, Inc. Of this number, 31 have been extruded into blanket rods. Twenty natural uranium, 2" diameter billets for fuel blanket rod have been completed. Eighteen of these billets have been extruded into fuel blanket rods. None of the enriched fuel billets has been assembled for extrusion.

Processing of the extruded blanket and fuel blanket rod upon return to ANL has just been started. A small number of the extrusions have been pickled, swaged, heat treated, and cut into blanket rods. All the equipment necessary for the performance of these operations has been built, assembled and tested.

III. ADVANCED ENGINEERING AND DEVELOPMENT - ACTIVITY 4530/4540/4580

1. Effects of Irradiation Upon ThO₂-UO₂ (J. H. Kittel)

The BORAX-IV reactor, which is fueled with ThO₂-6.36 w/o UO₂ highly enriched pellets, lead bonded to Al-1 w/o Ni tube-sheets, is arranged so that individual tubes of pellets can be irradiated and withdrawn from the reactor without disturbing the fuel configuration. The individual tubes, known as "bayonets," can thus be used to monitor irradiation damage to the fuel in the regular fuel elements.

Two bayonets were recently examined after they had been subjected to power excursions and short boiling runs. Although burnup in the fuel was negligible, the pellets had been subjected to thermal shock conditions as a result of reactor operations.

One of the bayonets, shown in Figure 12, contained 1X, 2X, and 4X pellets, i.e., 1, 2, and 4 times the normal amount of UO₂. The appearances of the pellets after removal of the aluminum alloy jacket and lead annulus are shown in Figures 13, 14 and 15. It can be noted that considerable fracturing has occurred, with some apparent dependence upon the amount of UO₂ in the specimens. The amount of burnup, temperature and thermal shock in the pellets were, of course, directly proportional to the UO₂ content.

In examinations of other bayonets at the Idaho site* no particular dependence of fracturing upon UO₂ content has been noted. Also, a pellet in an unirradiated control bayonet was found to have fractured.

These preliminary results indicate that fracturing in irradiated BORAX-IV fuel may not be greatly influenced by differences in operating conditions resulting from varying enrichments, and that some of the fracturing, at least, may be due to fabrication or handling procedures prior to irradiation.

2. Developments in Nondestructive Testing (W. J. McGonnagle, W. N. Beck, C. J. Renken)

a. Ultrasonic Fluoroscopy Unit

Two different methods applicable to the development of an ultrasonic fluoroscopy unit have been tested. The first system used a 196-segment mosaic, each segment of which was provided with an electrical connection. The output of the segments was coupled to individual transistorized amplifier circuits. The amplified signals were then applied to miniature neon tubes arranged in a pattern equivalent to the position of the crystals in mosaic.

*G. K. Whitham, private communication, May 24, 1957.

Figure 12. Bayonet Containing $\text{ThO}_2\text{-UO}_2$ Pellets After Irradiation in Borax-IV.

Macro 21791

1-X

Figure 13. 1X (6.36 w/o UO_2) Pellet From Above Bayonet.

Macro 21799

2-X

Figure 14. 2X (12.7 w/o UO_2) Pellet From Above Bayonet.

Macro 21796

2-X

Figure 15. 4X (25.4 w/o UO_2) Pellet From Above Bayonet.

Macro 21790

2-X

The system demonstrated satisfactory operation; however, each amplifier required frequent balancing to compensate for variations in the output of the individual segment of the crystal. The requirement for a number of amplifiers limits the practicality of such a system.

A second method tested employed a commutating system. Sixty segments of the mosaic were coupled to a mercury-jet switch. The commutated signal from the switch was connected to an amplifier, which in turn served to control the bias on a cathode-ray tube. A sweep circuit produced a raster on the cathode-ray tube, which was synchronized with the rotation of the mercury switch. In this manner the output of each crystal was presented on the raster in a position relative to its location in the mosaic and indicating by its comparative brilliance the intensity of the received ultrasonic energy. The system demonstrated that a commutating scheme is practical and simple. The resolution was far below the present scanning system; however, such a system would provide a scanner capable of detecting gross defects at high scanning rates.

b. Ultrasonic Thin-Plate Techniques

Experimental studies are being carried out on the transmission of ultrasonic waves through thin plates and laminated plates. Laminated plates used in the preliminary studies were made by plating stainless steel and nickel with copper of varying thicknesses.

An ultrasonic technique was used to detect shrinkage and porosity in cylindrical uranium castings to be used in the manufacture of EBR-I, Mark III fuel elements. These castings were 11" long and $2\frac{1}{2}$ " in diameter. A test frequency of 1 megacycle was used. A total of 89 such castings were inspected.

c. Clad-Thickness Measurements

An investigation has been started to determine the feasibility and usefulness of beta-ray back scattering for measuring clad thickness. The first experiments are being done on ALPR and Argonaut-type fuel elements. Radioactive strontium-90 has been used as a source of beta rays. An anthracene scintillator has been used as the detector system. The results obtained to date, using a fixed fuel element, indicate that the method can be used to measure cladding on ALPR and Argonaut-type plates. As is to be expected, thinner cladding can be measured to higher accuracy. Cladding on this type of fuel element in excess of 35 mils cannot be measured satisfactorily.

d. Development of Eddy Current Methods

A series of experiments have been initiated to determine optimum coil design for a given eddy current test situation. A theoretical

analysis of this problem is so involved that its solution is not likely in the near future; therefore experimental methods are being used. Determination of optimum coil design will make possible a new order of sensitivity in eddy current measurements.

Development work was continued on the eddy current system to be used in checking the welds and cladding of the EBR-I, Mark III fuel rods. The object of this work is to give the system a high order of long-term stability. Efforts are being made to correlate the results of the eddy current tests with metallographic inspection of the welds.

3. Corrosion

a. Corrosion-Resistant Uranium Alloys (S. Greenberg, J. E. Draley)

U-5 w/o Zr-1.5 w/o Nb: The study of the relationship between metallographic structure and corrosion behavior of these alloys is continuing. The electron microscope (with shadowed carbon replicas) is being used to detect possible submicroscopic phases.

Preliminary work, using conventional electrochemical etching procedures, can be interpreted in terms of a two-phase "as quenched" structure followed by agglomeration during aging, in line with the previously developed theory.

Uranium-Ruthenium: These alloys are of interest in that the beta phase can be stabilized at room temperature. In addition, ruthenium, or the uranium-ruthenium intermetallic compound, may act as a hydrogen getter.

Alloys containing 1, 2, and 5 w/o Ru were prepared by arc melting. All were gamma quenched from 900°C. In addition, the samples containing 1 and 5 w/o Ru were beta quenched from 675°C; it is not known as yet if the latter quench retained the beta phase, and alternate methods of heat treating will be studied.

The samples were tested in distilled water at 100°C for 2.9 days. Results are:

<u>Ru, w/o</u>	<u>Heat Treatment</u>	<u>Average Rate of Wt. Loss (mcd)</u>
1	Gamma Quench	35
2	Gamma Quench	36
5	Gamma Quench	27
1	Beta Quench	23
5	Beta Quench	191

Tests on these samples will continue. However, the results do not represent great improvement over unalloyed uranium. Efforts will be made to improve melting technique and heat treatment, as indicated above.

b. Corrosion-Resistant Aluminum Alloys
(W. E. Ruther, J. E. Draley)

Last quarter the measurement of the pH of phosphoric acid solutions at 290°C was described. The purpose in making these measurements was to have a basis for separating the effects of anions and pH in the high-temperature corrosion of aluminum alloys. Accordingly, testing was performed (M388 alloy) with a solution in which the pH at 290°C was equivalent to pH 4.5 (room temperature) H_3PO_4 but whose phosphate concentration (NaH_2PO_4) was equivalent to pH 3.5 (RT) H_3PO_4 (Test 4).

Another test was run with a solution in which the phosphoric acid concentration was that giving a room temperature pH of 4.5, but with sulfuric acid added to give a pH at 290°C equal to that of a pH 3.5 (RT) phosphoric acid solution (Test 3). The results of these tests, as well as some previously reported tests in phosphoric and sulfuric acids, are shown in Table II.

TABLE II
Corrosion of M388 Alloy^a at 290°C^b

Test	Components	pH at 290°C	Total PO_4^{3-} Conc.	Approximate Corrosion Rate After Initial Period (mg/dm ² /day)
1	H_3PO_4	4.8	$3.2 \times 10^{-5}\text{M}$	1.5
2	H_3PO_4	3.8	$3.3 \times 10^{-4}\text{M}$	Too low to measure, probably less than 0.1 mdd. Very little total corrosion.
3	H_3PO_4 , H_2SO_4	3.8	$3.2 \times 10^{-5}\text{M}$	Low rate - Scatter makes exact value uncertain. Probably less than 0.3. More total corrosion than Test 2.
4	H_3PO_4 , NaH_2PO_4	4.8	$3.3 \times 10^{-4}\text{M}$	Scatter - Rate about 3 mdd.
5	H_2SO_4	~3.6	0	2.0

^a1100 Aluminum plus 1 w/o Ni.

^bTest duration about 35 days.

The results indicate that both the pH and the anion are important. Comparison of Tests 1 and 4 shows that additional phosphate above that present in phosphoric acid was actually detrimental. This was unexpected, since phosphate has generally seemed quite beneficial.

A sizeable reduction in rate was achieved at the lower pH by the presence of a relatively small amount of phosphate ion (see Tests 3 and 5). Previous work (Test 2) has indicated that further slight improvement is obtained with more phosphate ion.

Dynamic Corrosion Testing: Previous work by the ANL Reactor Engineering Division has uncovered some unusual effects of velocity on the corrosion of M388 aluminum alloy, especially at temperatures below 315°C. Testing in our new dynamic facility has been started in an attempt to determine the factors involved. Test temperature is 260°C.

The first experiment used distilled water. Flow rates of about 2 and 22 feet/second were maintained in two sample channels. The samples were electrically insulated from the stainless steel to prevent galvanic effects. The feed solution was boiled by evacuation and then pressurized with 200 psig of tank hydrogen to reduce the corrosion of the stainless steel in the loop.

High-velocity samples (22 feet/second) loaded at the start corroded at a rate of ~13 mdd for the period of 5 to 11 days, and then commenced to corrode at the much higher rate of 45 mdd from 11 to 29 days (end of test).

Samples in the lower velocity section (~2 feet/second) corroded at roughly constant rates between 7 and 11 mdd after the initial period, depending on the individual sample. No break in rate was noted.

Samples added individually after the test had commenced (replacements for those removed) corroded uniformly at the high rate (~45 mdd) in the high-velocity channel. They also had about 1.8 times the corrosion of the original samples during the initial period. Replacements in the slower channel corroded only slightly more initially and the rates were not greatly different from those of the original samples.

This test was a success since it was specifically designed to maximize the flow and replacement sample effects. Hanford Atomic Products Division workers are attempting to explain these effects on the basis of the amount of aluminum ion in the solution. We are trying the hypothesis that it is the metal ions cathodic to aluminum (Ni^{++} , Fe^{++} , etc.) released by the corrosion of the aluminum alloy and the loop which are responsible for these large velocity effects. Another test has been started in which the effect of adding a small amount (0.5 ppm) of Ni^{++} (as NiSO_4) will be studied.

Eddy Current Thickness Gauge: As described in Metallurgy Division Quarterly Reports for 1953 and 1954, an eddy current device for nondestructively measuring the amount of aluminum corroded was developed for thin flat sheets. With the installation of the dynamic testing facility the sensing head was modified to accommodate the $1/2" \times 2" \times 1/8"$ dynamic samples.

Faults noted with the previous instrument have been largely overcome. Samples are pretreated for 10 days at the operating temperature of the test to prevent thermal effects in the thickness readings. The gauge is calibrated by defilming samples actually used in the corrosion test. Ultimate sensitivity is about $\pm 0.01 \text{ mg/cm}^2$ when used with M388 alloy.

This gauge is now being used as a standard tool in conjunction with the dynamic testing program and rates reported above were obtained through its use.

4. Fast Reactor Safety

a. Graphite-Urania Fuel Elements for the TREAT Reactor (J. H. Handwerk, R. C. Lied)

Mixtures of graphite-1 w/o urania containing from 5 to 20 w/o of an organic binder such as coal tar creosote, wheat flour, furfural, or a phenol-formaldehyde resin were cold pressed using a pressure of 35,000 psi. The compacts formed were found to have sufficient strength to permit handling and were of uniform appearance and free of any visible defects such as cracks. The as-pressed densities of these samples were found to be close to 1 gram/cc. This density was too low to meet the minimum fuel density specifications of 1.65 grams/cc for the reactor.

The use of higher forming pressures (up to 75,000 psi) produced compacts of higher density; however, only the compacts bonded with the phenol-formaldehyde resin were found to have pressed densities of at least 1.65 grams/cc. Forming pressures above 75,000 psi were not considered practical with the present laboratory equipment, and in order to produce dense compacts at lower forming pressures, the graphite-urania mixture containing the phenol-formaldehyde resin was pressed in steel molds heated to 200°C.

A mixture of 92 w/o graphite, 1 w/o U_3O_8 and 7 w/o phenol-formaldehyde resin (Bakelite BKS 2600) was mixed in a pebble mill with sufficient ethyl alcohol to form a thin slurry. The slurry was poured into a pan and the alcohol was evaporated. The dry "cake" was crushed, and this mixture was pressed in steel molds heated to 200°C using a pressure of 15,000 psi. The pressed pieces were packed in carbon black and heated

to 1500°C in an electric furnace. Samples thus formed were found to have densities in the range of 1.65 to 1.70 grams/cc. Radiographs of these samples revealed that the U_3O_8 was for the most part uniformly dispersed, and only an occasional small agglomerate was observed.

Samples of graphite- U_3O_8 mixtures which were fabricated by the United Carbon Products Company, Bay City, Michigan, were found to be rather severely worked, and several of the samples were found to be broken. Radiographs of these samples revealed that the U_3O_8 was uniformly dispersed in the graphite. The densities of these samples were found to be in the range of 1.69 to 1.75 grams/cc.

IV. PRODUCTION, TREATMENT, AND PROPERTIES OF MATERIALS - ACTIVITY 5410

1. Elastic Constants of Alpha-Uranium Single Crystals (E. S. Fisher, L. T. Lloyd)

The elastic constants C_{11} , C_{22} , C_{33} , C_{44} , C_{55} and C_{66} derived from ultrasonic wave velocity measurements in alpha-uranium single crystals at room temperature were reported in ANL-5717. For these constants, the waves were propagated parallel to the principal crystallographic axes. Of the nine fundamental elastic constants, C_{12} , C_{13} , and C_{23} remain to be derived. These constants affect propagated wave velocities only when the propagation direction is not parallel to one of the principal axes. Three specimens oriented for the determination of these constants are being prepared; their orientations and the basis for choosing them are discussed below.

The general equations of motion in anisotropic material of infinite dimensions have been derived by Green and Christoffel and are given by Love.¹ Green showed that, in general, when a plane vibrating wave front is generated in a crystal, three waves are produced. All of these have the same propagation direction (normal to the original wave front), but each has its own velocity and direction of vibration: In general, none of the vibration directions, or atom displacements, in the wave front is parallel to the propagation direction, but they are related to each other by being mutually orthogonal. Geometrically these directions form a strain ellipsoid where the three axes correspond to the three vibration directions. This phenomenon is analogous to double refraction of a light wave by a crystal where the incident light ray is divided into two rays polarized in mutually orthogonal directions which correspond to the index ellipse axes. The axes of the optic ellipsoid are characteristic of the symmetry and are independent of the incident direction. The strain ellipsoid axes depend, however, on the direction of wave propagation.

Christoffel derived a set of dependent equations which can be used for determining the theoretical velocities and vibration directions of the simultaneously generated waves moving in the same crystal direction. The general form of the equations relating the direction cosines of one of the three vibration directions to the elastic constants is:

$$\begin{aligned}\lambda_{11}\alpha + \lambda_{12}\beta + \lambda_{13}\gamma &= \rho c^2\alpha \\ \lambda_{12}\alpha + \lambda_{22}\beta + \lambda_{23}\gamma &= \rho c^2\beta \\ \lambda_{13}\alpha + \lambda_{23}\beta + \lambda_{33}\gamma &= \rho c^2\gamma\end{aligned}\quad , \quad (1)^*$$

¹A. E. Love, "The Mathematical Theory of Elasticity," Dover Publications, New York; 4th Edition (1944).

*Derivation of these equations can be found in reference (1).

where: λ_{ij} are functions of the elastic constants and the direction cosines (l, m, n) of the propagation direction relative to Cartesian coordinate axes X, Y, and Z; (α, β, γ) are direction cosines of one of the vibration directions relative to the same coordinate system; ρ = density of the material; and c = wave front velocity in the direction (l, m, n) .

The physical relations between the different factors become more apparent when equations (1) are written in matrix form:

$$[\alpha \ \beta \ \gamma] \begin{bmatrix} \lambda_{11} & \lambda_{12} & \lambda_{13} \\ \lambda_{12} & \lambda_{22} & \lambda_{23} \\ \lambda_{13} & \lambda_{23} & \lambda_{33} \end{bmatrix} = \rho c^2 [\alpha \ \beta \ \gamma] \quad (2)$$

In mathematical terms, there are three characteristic roots (or eigenvalues) of the three by three λ matrix denoted by ρc^2 . For each characteristic root there is a corresponding characteristic vector. It can be seen that the characteristic vector directions (α, β, γ) are unchanged by the system of homogeneous pure elastic strains denoted by the λ matrix; they correspond then to the strain ellipsoid axes, or three simple extensional strains into which the system can be resolved. The three roots are found, in terms of the elastic constants and direction cosines, by solving the characteristic determinant:

$$\begin{vmatrix} (\lambda_{11} - \rho c^2) & \lambda_{12} & \lambda_{13} \\ \lambda_{12} & (\lambda_{22} - \rho c^2) & \lambda_{23} \\ \lambda_{13} & \lambda_{23} & (\lambda_{33} - \rho c^2) \end{vmatrix} = 0 \quad (3)$$

Use of the Equations

General Use: The characteristic determinant is particularly useful in deriving the values of the elastic constants when the wave velocities are known from experiment. Since the λ elements are expressed in terms of the elastic constants, one obtains direct relations between the measured velocities the direction cosines l, m , and n ; the density, and the elastic constants which were involved in the displacements. Once the velocities and elastic constants are known, the vibration directions can be found from equations (1) and the relationship:

$$\alpha^2 + \beta^2 + \gamma^2 = 1 \quad .$$

Application for Determining Cross Constants of Uranium: Although the vibration directions depend on the direction of wave propagation in a crystal, it is only in special cases that these are parallel or transverse to each other. In general, all three waves have vibration components parallel to the longitudinal or shear wave vibrations generated by the transducers

attached to the crystal. The energy transferred to the crystal is shared by all three waves. This condition has an important adverse effect in the measurements of wave velocity. The precision of measurement depends considerably on the strength of the successive echoes on an oscilloscope pattern produced by wave reflections at the specimen faces parallel to the wave front. It appears important, then, to minimize the energy losses due to coupling effects, especially where the losses in energy associated with the small specimen size are already high.

For determining the elastic constants C_{12} , C_{13} , and C_{23} in orthorhombic crystals, ultrasonic waves have generally been propagated along directions which are perpendicular to one of the principal crystal axes and at intermediate angles to the other two. The reasons for selecting such orientations become apparent when one solves for the characteristic roots of equation (3).

For propagation perpendicular to the X axis, for example, the direction cosine l equals zero and m and n are finite. The expression for the λ 's as given by Cady² are:

$$\begin{aligned}\lambda_{11} &= m^2 C_{66} + n^2 C_{55} \\ \lambda_{22} &= m^2 C_{22} + n^2 C_{44} \\ \lambda_{33} &= m^2 C_{44} + n^2 C_{33} \\ \lambda_{23} &= mn (C_{23} + C_{44}) \\ \lambda_{13} &= \lambda_{12} = 0\end{aligned}\tag{4}$$

The resulting equation is factored into:

$$[(m^2 C_{66} + n^2 C_{55}) - \rho c^2] [(\rho c^2)^2 - (\rho c^2) (C_{44} [n^2 + m^2] + m^2 C_{22} + n^2 C_{33}) + \dots] = 0$$

One of the roots is immediately apparent: $\rho c^2 = m^2 C_{66} + n^2 C_{55}$

The vibration direction for this wave is obvious from inspection of the fundamental elastic constants involved. Both shear constants C_{55} and C_{66} involve elastic waves vibrating parallel to the X axis and traveling in a direction 90 degrees from X. For $m = 1$ (propagation along Y), $\rho c^2 = C_{66}$; for $n = 1$ (propagation along Z), $\rho c^2 = C_{55}$. For intermediate directions ρc^2 is as given above. This is, then, a pure transverse wave with vibration directions cosines, $\alpha = 1$ and $\beta = \gamma = 0$. From this wave velocity, cross checks are obtained for the previously determined values of C_{55} and C_{66} .

To determine expressions for the other two velocities, one solves the quadratic function for ρc^2 in terms of the known constants C_{44} , C_{22} , and C_{33} , the directions cosines l , m , and n , and the unknown constant C_{23} . Because the expressions for the two roots are complicated, the respective

²Walter Cady, "Piezoelectricity," McGraw-Hill Book Co., Inc. New York, p. 105 (1946).

vibration directions are not apparent from inspection of equations (1). However, since the pure transverse wave, the velocity of which is derived from λ_{11} , vibrates along the X axis, the other two vibrations must be 90° from X, or $\alpha = 0$. One can solve for the respective vibration direction for different propagation directions between the X and Y axes and for different assumed values of C_{23} . Although C_{23} has an important influence on the vibration direction, by assuming values within the range of its probable values, it can be shown for most cases that the wave with the greater velocity is close to longitudinal (vibrating close to the propagation direction m, n) and the other wave is correspondingly close to transverse. Experimentally one can determine C_{23} from the velocity of either the pseudolongitudinal or pseudo-transverse waves in a specimen with 2 flat faces which are perpendicular to the YZ or (100) plane.

The characteristic equations for $m = 0$ and for $n = 0$ are analogous to those for $\ell = 0$. For $m = 0$ the velocity of the pure transverse wave is a function of C_{44} and C_{66} and one determines C_{13} from the other two velocities. For $n = 0$ the transverse velocity is a function of C_{44} and C_{55} , and C_{12} is determined from the velocities of the coupled waves.

For each of the three specimens there is a choice to be made as to the propagation direction which is to be somewhere between the two principal axes not contained in the wave front plane. Considering only the equations for deriving C_{ij} from the measured wave velocity, it appears that the 45° direction would yield the best accuracy. This is true because the error in C_{ij} , for a given experimental error in determining the velocity, would be smallest for these orientations. However, it seems important to also consider how close the pseudolongitudinal wave may be to purely longitudinal, since a large deviation may have an important effect on the feasibility of obtaining adequate oscilloscope patterns.

The probable deviations from pure longitudinal vibrations have been calculated to enable a determination of the best propagation direction for evaluating the constants C_{12} , C_{13} and C_{23} . For example, to determine C_{23} where $l = 0$, values of ρc^2 for the two coupled waves were calculated for different values of m and n and for five different assumed values of C_{23} . For both waves $\alpha = 0$ and $\beta^2 + \gamma^2 = 1$. The vibration directions for the pseudolongitudinal wave for combinations of m, n and C_{23} were calculated from the equation:

$$\gamma = \left[\left(\frac{mn (C_{23} + C_{44})}{\rho c^2 - (m^2 C_{22} + n^2 C_{44})} \right)^2 + 1 \right]^{-1/2}.$$

For the wave to be purely longitudinal γ is equal to n.

Analogous equations were obtained for the other two specimens and the calculations were carried out by the AVIDAC computer. For the propagation directions perpendicular to the X axis, the results indicate that

the least deviation from longitudinal vibration would occur in a propagation direction 37° from the Z axis. In a 45° direction the deviation would be approximately 4° . For the directions perpendicular to the Y axis, the probable deviation at 45° is also approximately 4° ; however, the 45° direction seems to be the most satisfactory because all other directions between 30° and 60° show greater probable deviations. For the final specimen, the direction 45° to the Y and X axes is satisfactory, since, regardless of the value of C_{12} , the vibration direction of the pseudolongitudinal wave should be within 1.5° of the propagation direction.

In accordance with these results three single crystal specimens are now being prepared; the normals to the respective parallel faces are: 37° from the [001] direction towards the [010] direction, 45° between the [001] and [100] direction and 45° between the [100] and [010] directions. The faces are now in the final stages of preparation.

2. Plastic Deformation Mechanisms in Alpha-Uranium Single Crystals (L. T. Lloyd)

The preliminary high-temperature deformation studies of alpha-uranium single crystals reported in ANL-5623 demonstrated the feasibility of such experiments provided a dynamic vacuum of the order of 10^{-6} mm of mercury is maintained during the test. A bell jar vacuum system has been constructed to satisfy this condition and one crystal has been compressed at 600°C .

Equipment: An 18" diameter bell jar dynamically evacuated by a 6" vacuum system provides the protective atmosphere necessary for maintaining metallographic surfaces that are optically sensitive to polarized light after testing alpha-uranium single crystals at temperatures as high as 600°C . The specimen under test is heated by a small resistance-wound furnace located inside the bell jar, and temperatures are measured by a thermocouple located near the specimen. The crystal is deformed between parallel compression platens; one of these, supported by a thrust ball-bearing race, can move freely, as dictated by the deformation in the specimen, in a plane perpendicular to the compression direction. Load is applied to the crystal by a completely sealed hydraulic system. The upper platen is moved by a piston inside the bell jar. Pressure is generated in the hydraulic system by a piston located outside the evacuated bell jar. This piston is moved by a motor-operated gear train. Graphs of specimen contraction as a function of load are plotted directly on an X - Y recorder. The electrical signal for load is obtained from a Bourdon tube transducer sealed in the hydraulic system. Dimensional change is obtained from a linear variable differential transformer whose core is moved by a lever attached to the upper compression platen.

Crystal C₆: The first test with the above equipment was performed at $600^{\circ}\text{C} \pm 5^{\circ}$ on crystal C₆ oriented for compression in a direction 46° from the [100], 89° from the [010] and 44° from the [001] directions. Two parallel compression faces and five additional surfaces perpendicular to the compression faces were prepared on the crystal; two of the latter faces, inclined at 121° , were used as metallographic observation faces. The initial length between compression faces was 2.64 mm.

A macrophotograph of the crystal after a compressive deformation of approximately 20% is shown in Figure 16. A band of extensive slip may be seen running from the upper left-hand corner of face A to the lower right-hand corner of face B. Two-surface analysis of the trace directions resulted in the determination of the slip plane pole as lying 8° away from the (001) plane pole. This is in fair agreement with the results reported for crystal A₆ in ANL-5623. The slip appears to have occurred nonuniformly in that the common edge is offset in a stepwise fashion. Its extensive offset and the accompanying surface roughening prevent a detailed study of the markings.

Figure 16. Macrophotograph of Crystal C₆ after Approximately 20% Compressive Deformation at $600^{\circ} \pm 5^{\circ}\text{C}$.

The crystal did permit a determination of the slip direction for the (001) plane. The top of face A was displaced behind the bottom of face A by 0.060 mm and the top of face B extended beyond the bottom of face B by 0.344 mm. These measurements were made perpendicular to the face segments by means of the fine-focusing knob on a Bausch and Lomb Research Metallograph. The total contraction of the crystal was measured to be 0.543 mm. A combined numerical and stereographic analysis of these three displacement vectors resulted in a slip direction that lies within 10° of the [100] direction. No other low indices direction in the (001) plane lie close to this experimentally determined direction.

A determination of the critical resolved shear stress for slip on the (001) plane in the [100] direction was not possible for this crystal because its length dimension was too small. No (001) planes passed freely through the crystal, but rather they impinged upon one or the other compression platens. This fact probably also accounts for the geometrical deviation of the experimentally determined slip plane and slip direction from the (001) plane and [100] direction, respectively.

3. Thermal Expansion of Alpha-Uranium Single Crystals (L. T. Lloyd)

The earlier work on the thermal expansion measurements of alpha-uranium single crystals given in ANL-5153 demonstrated, physically, that the expansion coefficient in the b direction is negative. In order to obtain precise data it became evident that larger single crystals would be necessary and that the best directions of testing would be along the principal crystallographic axes. To this end, single crystals, 0.210" in diameter and up to 1/2" in length, have been prepared. Dilation curves have been obtained from two such crystals tested in a direction within 0.5° of the b axis (determined by Laue back-reflection photograms).

The specimens were prepared in the form of pseudounit cells. Techniques of isolating, orienting, grinding and polishing were similar to those given by Lloyd and Chiswik.³ Each crystal's initial length was measured in the [010] direction, after electropolishing and just before testing, to the nearest thousandth of a centimeter in a constant temperature room with a cathetometer. Four length measurements were made; the averages of these, converted to inches for crystals T_A and T_B, were 0.3059" and 0.2417", respectively.

Thermal expansion data were obtained from a recording quartz differential dilatometer. The crystals were heated over a temperature range of 23° to 650°C at a heating and cooling rate of approximately 4°C per minute. Each crystal was tested several times and the data were taken from a reproducible cooling curve because of the tendency of the dilatometer to lag behind the contraction of the sample during heating.

³L. T. Lloyd and H. H. Chiswik, "Deformation Mechanisms of Alpha-Uranium Single Crystals," ANL-5367 (December, 1954).

Metallographic observations of the six surfaces on each crystal prior and subsequent to testing indicated that only slight changes occurred. A few twins were present prior to testing, but the majority of these were absorbed during the first few tests. After final testing only two or three fine twins were observed on the surface of each crystal. No evidence was observed of recrystallization. A thin oxide film formed on both crystals during testing; however, its thickness was not sufficient to significantly change the length dimension and it was easily removed by electropolishing.

The results obtained for the two crystals are tabulated in Table III in terms of inches expansion per inch of original length as a function of temperature. The values have been corrected for the expansion of quartz over the specimen length. For comparison, the dimensional changes for the [010] direction, as calculated from the X-ray lattice parameter data reported by Bridge, Schwartz, and Vaughan,⁴ are also tabulated. Figure 17 is a graphic presentation of the data.

TABLE III
Expansion of Alpha Uranium in the [010] Direction

Temperature (°C)	Expansion in the [010] Direction* (in./in. x 10 ⁴)		
	Crystal T _A	Crystal T _B	Calculated from Equation**
50	- 0.10	0.08	0.08
75	0.00	0.08	0.11
100	- 0.07	0.16	0.07
125	- 0.59	- 0.50	- 0.08
150	- 1.08	- 0.60	- 0.34
175	- 1.60	- 1.04	- 0.72
200	- 2.48	- 1.66	- 1.36
225	- 3.79	- 2.44	- 1.96
250	- 5.10	- 3.76	- 2.85
275	- 6.60	- 5.17	- 3.93
300	- 8.30	- 7.12	- 5.23
325	-10.00	- 8.77	- 6.77
350	-12.13	-10.72	- 8.56
375	-14.46	-12.91	-10.61
400	-16.74	-15.43	-12.96
425	-19.65	-18.45	-15.60
450	-22.59	-21.52	-18.57
475	-25.73	-24.87	-21.87
500	-28.83	-28.51	-25.53
525	-32.40	-33.02	-29.56
550	-36.74	-37.36	-33.98
575	-41.52	-42.57	-38.81
600	-47.11	-47.87	-44.06
625	-52.31	-53.46	-49.75
650	-57.93	-59.54	-55.90

*Based upon 1" specimen length at 25°C.

**The equation for expansion in the [010] direction, as derived from the data of Bridge, Schwartz and Vaughan, is:

$$L_T = L_0^\circ C (1 + 0.61 \times 10^{-6}T - 2.17 \times 10^{-9}T^2 - 18.41 \times 10^{-12}T^3)$$

where: L = length, and T is expressed in °C.

⁴J. R. Bridge, C. M. Schwartz, and D. A. Vaughan, "X-ray Diffraction Determination of the Coefficients of Expansion of Alpha Uranium," Trans. AIME 206 1282 (1956)

Figure 17. Expansion of Alpha Uranium Single Crystals in the [010] Direction as a Function of Temperature.

Macro 21814

The curves from the single crystals fall slightly below the one obtained from lattice parameter measurements. The greatest deviations between the two types of curves occur above 100°C. This may be attributed to the restraining effects that could occur in polycrystalline materials used for determining the lattice parameters by X-ray methods. In such methods, filings annealed at 600°C prior to test were used; very probably each filing was polycrystalline. The expansion in the a and c directions could have a restraining effect upon the contraction in the b direction and prevent the expansion from being as negative as possible. In the single crystals there would not be such a restraining effect.

4. Recrystallization of Heavily Cold-Rolled Uranium Sheet (W. R. Yario, L. T. Lloyd)

The investigation of recrystallization in alpha uranium without a texture change, reported by Cabane and Petit,⁵ has continued during this quarter. Dilatation studies reported in ANL-5709 showed that the changes in mean expansion coefficient between 200° and 300°C for annealed specimens over that measured for an as-cold-rolled specimen was not a simple function of the measured volume per cent recrystallization. At low annealing temperatures and correspondingly low percentage recrystallization the coefficient changed very little, whereas at higher temperatures and greater percentage recrystallization the change in coefficient was more pronounced. A metallographic study of specimens annealed for short times at 400°C, and for long times at 360°C, was reported in ANL-5717. During the early stages of recrystallization, relatively large grains were observed in the process of absorbing extremely fine recrystallized grains, indicating two operating recrystallization mechanisms.

Dilatation tests have been performed on samples of high-purity uranium annealed for short times at high temperatures and long times at low temperatures to investigate the relationship between relative amounts of large and small grains and texture change. Since insufficient high-purity material remained to machine additional dilatometry specimens, the final portion of ingot HPX-16 was fabricated for this study. An attempt was made to heat treat and fabricate the second sheet exactly like the first. Dilatometry and metallographic specimens were cut from this sheet and annealed for various times at 320°, 360° and 400°C. The tests were performed using the methods described previously. The data for HPX-16 specimens are given in Table IV.

TABLE IV
Volume Per Cent Recrystallization and Change in Mean Expansion Coefficients of
Heavily Cold Rolled Uranium Sheet after Various Annealing Treatments*

Annealing Treatment		High-Purity Uranium (HPX-16)		French Uranium (Sheet N)	
Temperature (°C)	Time	Volume Per Cent Recrystallization	Change of Mean Expansion Coefficient (in./in. - °C × 10 ⁶)	Volume Per Cent Recrystallization	Change of Mean Expansion Coefficient (in./in. - °C × 10 ⁶)
320	200 hr	72	0.11, -0.26	30	-0.47
320	400 hr	85	2.13, 2.26	-	-
360	92 hr	91	0.95, 0.11	57	-0.82
360	165 hr	-	-	58**	-
360	200 hr	98	1.22, 0.95	65	-0.58
400	2.5 min	49**	-	-	-
400	3.5 min	62	0.45	-	-
400	5 min	82**	0.71	-	-
400	15 min	81, 85**	0.57, 0.94	-	-
400	30 min	88	2.75, 2.28	51	-0.08
400	1 hr	91	3.49, 4.82	-	-
400	15 hr	99	5.52, 4.22	84	0.63
450	15 hr	-	-	100	1.86

*Change in mean expansion coefficient between 200° and 300°C over the average obtained from 2 cold-rolled specimens. Dilatation tests were made in a direction perpendicular to the rolling direction and lying in the rolling plane.

**Value determined from separate metallographic sample. All other per cents recrystallization were measured from dilatation samples after testing.

⁵G. Cabane and J. Petit, "Study of the Annealing of Rolled Uranium,"
Revue de Metallurgie 51 603-613 (1954).

Figure 18 is a plot of the volume per cent recrystallization at 400°C as a function of the logarithm of the annealing time. The specimens from the second sheet of HPX-16 have higher volume per cent recrystallization for equal periods of annealing time than did the specimens obtained from the first sheet (ANL-5717). This suggests that, even though every attempt was made to do so, the thermal and fabrication histories of the materials were not exactly the same. It also indicates that the volume per cent recrystallization for a given annealing treatment is extremely sensitive to variations in fabrications processes.

The data for the change in the transverse mean expansion coefficients of samples annealed at 400°C are similar to those reported in ANL-5709 for samples annealed at various temperatures and for a constant period of 15 hours. Up to 80% recrystallization there is essentially no change in texture, as measured by the change in mean expansion coefficient; however, the texture changes rapidly upon further recrystallization. The values of change in mean expansion coefficient for volume per cent recrystallizations between 80 and 90% are somewhat lower than those given in the previous curve; however, the coefficient for more than 90% recrystallization is nearly the same. The interesting point is that, by annealing for long periods of time at lower temperatures, as high as 98% recrystallization can be obtained with only a small change in mean expansion coefficient. The data for the samples annealed 400 hours at 320°C are an exception to this.

The results indicate that the change in texture might be correlated with the absorption of small recrystallized grains by larger ones for the 400°C annealed samples because it occurs simultaneously with the absorption of almost all of the fine grained material. The 320°C annealed samples showed fine grains after treatment. Two of these, annealed for 400 hours, showed an appreciable change in texture, whereas the samples annealed for 200 hours showed only a small change. The 360°C annealed samples, on the other hand, showed relatively large grains after long periods of annealing but small changes in texture. Thus, there appears to be no consistent correlation between the absorption of fine grains by larger ones and the texture change.

The results indicate that, for constant volume per cent recrystallization, a smaller change in mean expansion coefficient accompanies recrystallization at lower temperatures. This agrees with the observation of Cabane and Petit that heavily cold-rolled uranium sheet may be recrystallized at low temperatures with little or no texture change.

Tests of French Uranium - Sheet N: Some metallographic and dilatation studies have been performed on the French uranium furnished in cold rolled sheet form by Cabane.* This material is from the same

*Saclay Laboratory, France.

Figure 18. Volume Percent Recrystallization of Heavily Cold-Rolled Uranium Sheet as a Function of the Logarithm of Annealing Time at 400°C.

Macro 21813

Figure 19. Change of Mean Expansion Coefficient of Uranium Sheet Between 200° and 300°C, Over That Obtained from Two Cold-Rolled Specimens, as a Function of the Volume Percent Recrystallization.

Specimens were annealed for varying times at the indicated temperatures. Dilatation tests were performed in a direction perpendicular to the rolling direction and lying in the plane of rolling.

Macro 21812

ingot studied by Cabane and Petit. The volume per cent recrystallization and change in mean expansion coefficient data are given in Table IV.

The general metallographic features of the French material were similar to those observed in the high-purity uranium and reported in ANL-5623 and ANL-5717. For a given annealing treatment the volume per cent recrystallization was smaller. This corresponds to the lesser purity as indicated by the analyses given in ANL-5623 and may also be related to slight differences in metallurgical history. Fine-grained areas in the process of being absorbed by relatively large grains, as illustrated in Figure 20, were observed in all specimens except the one completely recrystallized by annealing at 450°C.

Figure 20. French Heavily Cold-Rolled Uranium Sheet
Annealed at 400°C for 15 Hours.

(84 Percent Recrystallization)

Micro 21747

Polarized Light

1000-X

The data for change in mean expansion coefficient are somewhat more scattered than are the HPX-16 values. Complete recrystallization at 450°C does not result in as large a change in mean expansion coefficient as it does in HPX-16 (ANL-5709).

5. Self-Diffusion in Uranium

(S. J. Rothman, L. T. Lloyd)

Refining of Highly Depleted Uranium: The highly depleted uranium reduced by Mallinckrodt has arrived at Argonne. The material is being re-melted. The reductions were not very good; only about half of the material is in the form of biscuits, the rest being shotted through the slag. Changes for a high percentage recovery seem very slim.

Barrier Layers Showing Sputtering: Previous experiments on self-diffusion in gamma uranium have resulted in no penetration of U^{235} into the sample. The possibility of a barrier layer at the interface between the base metal and the sputtered layer has been mentioned in ANL-5709 and ANL-5717. Metallographic studies have determined that such a layer is present, and that it is mainly UO_2 . The rest of this report is devoted to the discussion of the test performed to determine the presence of such a layer.

In the first of these experiments, zirconium metal was sputtered onto a 1/8" diameter, normal uranium pin; zirconium was used so that any penetration could be detected metallographically. Both the uranium pin and the zirconium cathode remained bright during the sputtering process. Both were, of course, cleaned by ion bombardment before depositing the zirconium. After sputtering, the pin was broken in two; it had been notched to facilitate breaking. One half was nickel plated, to protect the sputtered layer during polishing, and examined metallographically. The other part was encapsulated as follows: transfer quickly to a quartz capsule, flush capsule 5 times with purified argon, evacuate to about 2×10^{-6} mm Hg, degas the sputtered layer by heating slowly to $450^\circ C$, hold for one hour and cool slowly, flush capsule with purified argon and seal off under a partial pressure of purified argon. This sample was diffusion annealed by heating slowly to $950^\circ C$, holding for 3 days, and cooling slowly. It was then nickel plated and examined metallographically.

The as-sputtered zirconium-uranium specimen is shown in Figure 21-a, and the annealed specimen in Figure 21-b. The as-sputtered zirconium looks very much like the dark-layered, mottled structure that has been observed many times on sputtered uranium samples in both as-sputtered and alpha-annealed conditions. The layering is probably due to interruptions in the sputtering process.

The annealed structure is strikingly different from the as-sputtered. The entire layer is much thicker, there is a thick UO_2 layer at the interface, only two of the eight thin layers remain, and the outermost layer, which is probably alpha zirconium, is much lighter in color and is severely cracked.

The development of this annealed structure from the as-sputtered layer is difficult to explain. The O_2 which formed the oxide was undoubtedly co-deposited with the zirconium during sputtering. It was (a) either present

Figure 21. Zirconium Sputtered on Uranium.

21-a. As-Sputtered

Micro 21570 2000-X
As Mechanically Polished

21-b. Annealed 3 Days at 950°C

Micro 21589 As Mechanically Polished 2000-X

as an impurity in the sputtering gas; (b) it was liberated from the cathode and other components inside the bell jar by the action of the gaseous discharge; and/or (c) there may have been a leak in the system.

It may be shown that the annealing gas does not contain enough O_2 to give rise to such a thick UO_2 layer. If one considers that the capsule has a volume of about 5cc, and that this is filled to about $1/4$ atmosphere with gas containing 0.07% O_2 , one obtains about 3.5×10^{-8} mole of O_2 in the capsule. This much oxygen would form 1.3×10^{-6} cc UO_2 , or, on a sample 1 cm long and $1/8$ " in diameter, it would form a layer about 10^{-6} cm thick. This is about 1000 times thinner than that observed.

An analogous calculation has been made for the sputtering gas. Assuming a constant O_2 concentration of 10^{-6} mm Hg, and considering that the 7.5-micron thick zirconium layer was deposited in 15 hours, we find that the number of zirconium atoms impinging on the sample per cm^2 per second is of the same order of magnitude as the number of oxygen molecules impinging on the same area in the same time.

During the diffusion anneal, the oxygen diffused to the interface and oxidized the uranium. Judging from the irregularity of the oxide layer inner boundary, the U- UO_2 interface advanced into the metal (anion diffusion through the UO_2). The alpha zirconium may have become lighter in color due to the removal of the O_2 that had been dissolved in it. This layer may have cracked because of stresses due to phase transformations, thermal stresses, or stress corrosion in the acid nickel-plating bath. No explanation is offered for the two thinner layers between the UO_2 and the zirconium; they do not correlate with any of the structures in the as-sputtered material.

A similar experiment was run with uranium sputtered on uranium. This time two notches were cut into the sample. One part of the sample was diffusion annealed in a high vacuum (2×10^{-6} mm Hg), and another in purified argon. Otherwise the treatments were the same as for the Zr-U sample. Copper was plated on the samples from a cyanide bath; it was hoped that the possibility of stress corrosion cracking would thus be obviated. Figure 22 shows microstructures of the vacuum-annealed sample; Figure 23 shows microstructures of the one annealed in argon.

The general appearance of these samples is quite out of the ordinary. For the first time, a reasonable metallographic structure that does not consist entirely of the dark, mottled material as shown in Figure 21-a has been developed in the sputtered layer. The main body of the sputtered layer is the same color as the base metal. This result may be attributed to the fact that these samples were annealed in the gamma range and therefore went through phase transformation, while previous samples were only

Figure 22. Uranium Sputtered on Uranium and Vacuum Annealed 3 Days at 950°C.
(All micros as mechanically polished)

22-a. Compare Relative Absence of Oxidation with Figure 23-a.

22-b. $U(C,N,O)$ Inclusions.

22-c. UO_2 , UC, and $U(C,N,O)$ Inclusions.

Figure 23. Uranium Sputtered on Uranium and Annealed 3 Days at 950°C in Purified Argon.

(All micros as mechanically polished)

23-a. Note thickness of oxidized layer next to the copper.

23-b. Fully oxidized section of sputtered layer is shown. This is similar to earlier alpha annealed samples.

23-c. Same as above at higher magnification.

alpha annealed. Only the outside part of the sputtered layer has the dark, mottled structure. There are many inclusions in the sputtered layer, and an almost continuous layer of them at the interface.

Three, or possibly four, different types of inclusions are present. The straight-sided, light-colored inclusions (#1, Figure 22-c) are UC. The large, dark, straight-sided inclusions (#2, Figure 22-c) are UO_2 . The identity of the light grey inclusions (#3, Figure 22-c and #4, Figure 22-b) is uncertain; they are probably $\text{U}(\text{C},\text{N},\text{O})$. It has been suggested⁶ that these two types of inclusions represent different compounds. On repolishing or electropolishing, or under oblique illumination, the light grey inclusions become almost as dark as the UO_2 . X-ray powder patterns of material scraped off the inside of the copper plate showed only UO_2 . Patterns of the material on the surface of the specimen itself showed UO_2 and a face-centered cubic phase which may be UN, UC, or a solid solution of $\text{U}(\text{C},\text{N},\text{O})$. Because of the conditions under which the X-ray pattern was taken, no determination of the lattice parameter of the latter inclusion could be made, and therefore the inclusion cannot be definitely identified.

The vacuum-annealed sample was much cleaner than the one annealed in argon. There was a smaller quantity of inclusions at the interface, there was a thinner oxidized layer at the outside, and a smaller fraction of the sputtered layer was totally oxidized in the vacuum annealed sample. The argon-annealed sample, however, was much dirtier than the above calculations indicate it should be.

The difference between the microstructures of the Zr-U and U-U couples can be explained on the basis of the high solubility of O_2 in zirconium. The sputtered zirconium will contain much more O_2 than the sputtered uranium. During the high-temperature anneal, the O_2 will be taken up by the uranium; free energy considerations favor this reaction slightly.⁷ Whatever O_2 is taken into solution by the sputtered uranium goes to form the outside oxidized layer, the inclusions at the interface, and the inclusions in the sputtered layer. Whatever O_2 is in the annealing atmosphere seems, strangely enough, to diffuse to the interface as well as to help thicken the outside oxidized layer, but does not appear to affect the inclusions within the sputtered layer. The possibility for O_2 pick-up in transposing the sample from the bell jar to the capsule should also be pointed out. The argon and vacuum-annealed uranium on uranium samples were exposed to air for the same length of time. However, the Zr-U specimen was exposed for a shorter time.

⁶These suggestions were made by Prof. G. L. Kehl, Columbia University, to whom we are indebted for very fruitful discussions.

⁷O. Kubaschewski and E. Evans, "Metallurgical Thermochemistry," 337-338, John Wiley, New York (1956).

Some of the inclusions appearing at the interface are probably formed during the cleaning operation. It has been pointed out⁶ that an ion bombarded surface can get quite hot, which, in the case of uranium, would lead to a ready combination with whatever impurities are present in the gas, or adsorbed on the surface. In other words, contaminants which may be present on the electropolished surface may be fixed by ionic bombardment.

Uranium impurity compounds may also be formed in the gas phase during sputtering and diffuse back to the sample. The gas mean free path in a glow discharge at pressures of 10 - 20 microns is less by one or two orders of magnitude than the distance between cathode and sample.⁸ Although the uranium atoms leave the cathode with much higher velocities than the thermal velocities of the gas atoms, some of them will still diffuse back. If these nascent uranium atoms combine with O₂, say, the UO₂ molecules can also diffuse back.

These microstructures cannot be reconciled with the ones of alpha-annealed sputtered uranium that have been obtained previously. Nor can the barrier layers be reconciled with Weil's statement⁹ that diffusion can be obtained between sputtered zirconium and uranium.

These results obviously cast grave suspicion on the purity of the gas used for sputtering. A sample of the gas was therefore analyzed mass spectrographically by Dr. B. D. Holt of the Chemistry Division. The analysis showed (in %): H₂ - 0.06, O₂ - 0.07, CO₂ - 0.02, N₂ and CO - 0.08, H₂O - 0.23. The last value is quite uncertain and may be disregarded. Nevertheless, this is considerably less pure than tank gas.

To avoid these conditions, and to return to the gas-purity conditions under which Weil observed diffusion, new charges have been put into the gas train components. It was noticed that the P₂O₅ that was removed was very pure and powdery, which would not be the case if large amounts of argon containing approximately 0.2% H₂O vapor had been passed through it. Similarly, the uranium chips were quite shiny, and the other components also seemed to be in good condition. There was no obvious evidence of gas channeling. This points to the possibility of a leak in the system, which is being investigated. Further, modifications of the bell jar base plate are being made which will allow both water cooling and placing the sample into a capsule without taking it out into the air.

6. Uranium Alloys

a. The Uranium-Carbon System (B. Blumenthal)

Alpha-Beta Transformation of U-C Alloys: The general method that was used for determining the alpha-beta transformation of high-purity

⁸A. Guenterschultze and K. Meyer, Zeits. f. Phys. 62 607 (1930).

⁹R. Weil, private communication

Uranium was applied to a uranium-carbon alloy prepared by induction melting high-purity uranium in a high-purity graphite crucible and casting into a water-cooled copper mold. Only one change was made: the bare specimen

TABLE V

Alpha-Beta Eutectoid Transformation
Temperatures of Uranium-Carbon
Alloys (Ingot B-727-B)

Heating or Cooling Rate (°C/min)	Mean Eutectoid Temperature (°C)	
	Heating	Cooling
4	673.0	660.2
2	673.1	660.7
1	672.7	661.5
0.5	671.0	662.1
0.33	669.9	662.2
0.167	669.8	661.9
Extrapolated Equilibrium Values		
0.0033	664.9	

was suspended in the thermal analysis furnace. This arrangement eliminated the urania crucible support and enhanced heat transfer conditions to and from the specimens. A considerable difference between the arrest temperatures for heating and cooling still persisted; this, however, decreased with decreasing rates of heating or cooling (Table V). As in the case of high-purity metal, it was reasonable to assume a straight line relationship between the arrest temperatures and the logarithm of the rate of heating or cooling. Application of the method of least squares to the data yielded the functions

$$T_H = 671.89 + 2.82 \log r$$

$$T_C = 661.27 - 1.46 \log r,$$

where T_H and T_C are the transformation temperatures in °C on heating and cooling, respectively, and r is the rate of heating or cooling in °C/minute. The two lines intersect at the equilibrium transformation temperature of 664.9°C. Equilibrium would be attainable at a rate of 3.3×10^{-3} °C/minute. Since the equivalent temperature for high-purity uranium is 669.0°C, the alpha-beta transformation of the uranium-carbon alloys is of the eutectoid type. Confirming experiments are in progress.

Beta-Gamma Transformation of U-C Alloys: In applying the same method to the beta-gamma transformation of an uranium-carbon alloy, satisfactory arrests were obtained on cooling. Since several degrees of supercooling occurred, the constant temperature obtained after recalescence was regarded as the correct transformation temperature. Difficulties arose in obtaining the arrest temperatures on heating, since the transformation occurred over a temperature range. At the slower rates the midpoint of the arrest temperature range was easily read from the curves, whereas at higher rates the midpoint was determined by geometric means. On the other hand, the beginning of the temperature arrest was distinct in all cases. Data for both the midpoint and the beginning of transformation were obtained and evaluated. The mean corrected data are listed in Table VI; they yield by the method of least squares the functions

$$\begin{aligned}
 T_H (\text{initial}) &= 772.57 + 0.51 \log r \\
 T_H (\text{midpoint}) &= 776.21 + 2.41 \log r \\
 T_C &= 766.01 - 2.81 \log r
 \end{aligned}$$

The symbols are self-explanatory. The points of intersection of each pair of equations are:

$$\begin{aligned}
 \text{for } T_H (\text{initial}) \text{ and } T_C &- 771.56 \text{ at } 1.1 \times 10^{-2} \text{ }^\circ\text{C/minute} \\
 \text{for } T_H (\text{midpoint}) \text{ and } T_C &- 771.51 \text{ at } 1.1 \times 10^{-2} \text{ }^\circ\text{C/minute} \\
 \text{for } T_H (\text{initial}) \text{ and } T_H (\text{midpoint}) &- 771.59 \text{ at } 1.2 \times 10^{-2} \text{ }^\circ\text{C/minute}.
 \end{aligned}$$

All three lines intersect at one point. By extrapolating the arrest temperatures to the point of intersection the differences between the beginning of transformation and the midpoint disappear, as they should if the observed data represent a horizontal in a binary system. It is concluded that 771.6°C is the equilibrium temperature.

TABLE VI

Beta-Gamma Transformation Temperatures
of Uranium-Carbon Alloys

Heating or Cooling Rate ($^\circ\text{C/min}$)	Mean Transformation Temperature ($^\circ\text{C}$)		
	Heating		Cooling
	Initial Point	Midpoint	
2.223	773.6	777.4	766.1
0.741	772.2	775.9	768.3
0.371	771.2	773.8	767.7
0.185	772.8	775.4	769.5
Extrapolated Equilibrium Values			
0.0011	771.6		

As yet, only one set of data has been obtained for the beta-gamma transformation of high-purity uranium. At a rate of $0.89^\circ\text{C/minute}$, high-purity uranium (Ingot B-724) transforms at 775.3°C on heating (midpoint) and at 771.1°C on cooling. This is close to the data reported in Table VI. On the basis of the data for cooling, an eutectoid-type transformation for the beta-gamma transformation of uranium-carbon alloys may be inferred.

The Melting Point of Uranium: As part of the thermal studies of the U-C alloys, the melting point of high-purity uranium has been re-determined. The data reported in ANL-5717 have been confirmed. The mean value of the melting point of three high-purity ingots is $1131.4 \pm 0.4^\circ\text{C}$, that of the freezing point is $1133.1 \pm 0.4^\circ\text{C}$. Again the freezing temperature is higher than that of melting due to the presence of a temperature gradient in the metal. The equilibrium temperature is assumed to be the mean between melting and freezing, i.e., $1132.3 \pm 0.5^\circ\text{C}$.

b. Uranium-Molybdenum and Uranium-Ruthenium Systems
(A. E. Dwight)

The β to α transformation of uranium is lowered by additions of either molybdenum or ruthenium. In both systems metastable β can be retained at room temperature by water quenching a small specimen from the β range. In the U-Ru system, β transforms eutectoidally to $\alpha + \text{U}_2\text{Ru}$ at $640 \pm 5^\circ\text{C}$. In the U-Mo system the eutectoid temperature is $628 \pm 3^\circ\text{C}$. The compositions of the eutectoids have not yet been determined. Transformation temperatures were determined by isothermally transforming small, needle-shaped specimens for times ranging from 3 hours to 16 days, quenching in water, and taking Debye-Scherrer patterns at room temperature.

c. Uranium-Molybdenum-Ruthenium System (A. E. Dwight)

Figure 24 shows the experimental alloys which have been under investigation during the past quarter. All alloys were annealed at 900°C for periods ranging from 3 days to 1 week, and water quenched. The γ uranium phase in all alloys was retained at room temperature. Lattice parameters shown in Figure 24 were measured with a flat plate back-reflection camera. Metallographic examination established the existence of the two- and three-phase regions.

d. Properties of Uranium-Fissium Alloys (M. V. Nevitt,
S. T. Zegler)

An evaluation of alternative experimental methods of measuring thermal conductivities of uranium-fissium alloy specimens has been completed. A modification of the Shelton-Van Dusen method, similar to that employed at Battelle Memorial Institute, has been selected; equipment and fittings for the apparatus are being acquired.

7. Basic Corrosion

a. Aqueous Corrosion of Aluminum (S. Mori, J. E. Draley)

The long-term tests (over 900 days) of 1100 aluminum in distilled water at 50° and 70°C , and in potassium sulfate solution at 70°C , have now been completed. Preliminary results, reported last quarter, have now

Figure 24. Isothermal Section of Uranium-Molybdenum-Ruthenium System at 900°C and Gamma Uranium Phase Lattice Parameters (Absolute Angstroms).

Macro 21785

been confirmed, that is, corrosion apparently proceeded at a continuously decreasing rate. It has not been possible to distinguish between two basic equations to express the relation between weight gain and time in distilled water:

$$(1) \quad \Delta W = at^b, \text{ and}$$

$$(2) \quad \frac{1}{\Delta W} = A - B \log t \quad .$$

The second type of equation has previously been used to explain the growth rates of some very thin films.

The presence of dissolved potassium sulfate inhibited the corrosion reaction during initial periods, lasting up to several months. Subsequent to that time, rates became roughly equal to those in water.

The pH of the water immediately adjacent to rapidly corroding 1100 aluminum samples has been shown to vary with vertical position along

the metal. Near the surface the water has been most alkaline, with pH decreasing with increasing depth along the sample.

b. Zirconium-Corrosion Mechanism (R. D. Misch, F. H. Gunzel)

The resistances of the corrosion oxide on a series of zirconium-titanium alloys (0.05, 0.10, 0.25, 0.50 w/o Ti) have been measured by using evaporated aluminum spots. The corrosion films were prepared by exposure to water at 290°C. Films which are too thin are easily damaged so that thicknesses above 5000 Å are desirable.

The following were observed at room temperature:

- (1) The oxide was insulating on all specimens with undamaged films. The resistivity was 10^{13} to 10^{14} ohm-cm.
- (2) As customary with insulators, the resistance was lowered by an increase in field strength. The relation was exponential, such that $\log R$ vs. E yielded a straight line. The maximum field strength to which the films were subjected was of the order of 10^4 volts/cm (1 volt across a film 10,000 Å in thickness).
- (3) The emf in the specimen was dependent upon the environment. In air the polarity was such that the zirconium was always positive relative to the aluminum. The emf's were as high as 0.46 v, although generally lower. In vacuum the emf diminished and generally the polarity reversed. A slow drift of emf with time indicated that a reversal in polarity could always be expected. A typical emf in vacuum was -0.070 v (Zr negative).
- (4) The resistances of the films were independent of polarity so that rectification was not detectable under these conditions. Upon heating in vacuum the following effects were observed:
 - (a) The resistivity decreased to the order of 10^{10} ohm-cm at 185°C.
 - (b) The dependence of resistance on field strength became much smaller, but was still significant at 200°C.
 - (c) The emf became positive with heating but generally began to drop before or after reaching 185°C. The extent of these changes varied with the specimen.

8. Sintering of Ceramic Materials (L. L. Abernethy, G. C. Kuczynski*)

Sintering experiments were made on single-crystal synthetic sapphire spheres placed on ground and polished single-crystal synthetic sapphire plates. Heating was accomplished in a molybdenum-wound, alumina-tube furnace in a hydrogen atmosphere. During each run, approximately 35 to 40 30-mil spheres were placed on each 1/4" diameter by 1/16" thick plate. A short length of 1/4" I.D. alumina tubing was placed around each plate to prevent spilling of the spheres during placement in the furnace.

After heating, the spheres were broken from the plates and the residual stumps of the interfaces between spheres and plate were measured, using a microscope with micrometer eyepiece and vertical illumination. Figure 25 shows the relationship between the rate of interfacial, or neck, growth and sintering time after heating intervals of 4, 18, 36, and 48 hours at 1800°C. The inverse slope of this curve, i.e., $n = 4.12$, would indicate that the mechanism of sintering of Al_2O_3 is a diffusion process by being close to a fifth power relation. A depressed area could be observed around the residual stumps on the plates; this would be consistent with a volume-diffusion process, with deposition of vacancies on the surface of the plate around the interface.

Figure 25. Neck Growth Versus Sintering Time for 30-mil Alumina Spheres Sintered in Hydrogen Atmosphere at 1800°C.

*University of Notre Dame; Consultant to the Metallurgy Division at ANL.

As shown in the photographs, Figures 26-a through -d, the stumps of the necks were not always round. An approximate diameter was determined from four measurements of each stump, and the average diameter of 12 or more stumps was used to determine the value of each point on the graph. The outlines of the residual necks were very irregular for short sintering times, but were nearly circular after 48 hours of heating. Some of the stumps show evidence of hexagonal symmetry, particularly after 48 hours of heating. The residual stumps of the interfaces appear to have flat surfaces, as if they were broken along a cleavage plane. The plates used in these experiments were cut and polished so that the 0001 plane was in contact with the spheres. Al_2O_3 has perfect cleavage along the 0001, or basal, plane only. This observation would indicate that the material in the neck assumed the same crystallographic orientation as the plate.

Pores were observed in some of the necks; they appear to have been formed by the growth of fingers or islands of material (between sphere and plate), which later joined together to form closed voids. When spheres sintered to spheres were broken apart, and the residual interfaces were examined under a microscope, the same irregularity of outline was observed, along with isolated closed pores.

Figure 26. Residual Necks of Thirty-mil Alumina Spheres Broken from Alumina Plate After Sintering in Hydrogen Atmosphere at 1800°C.

26-a. Sintered 4 Hours

26-b. Sintered 18 Hours

26-c. Sintered 36 Hours

26-d. Sintered 48 Hours

V. ALLOY THEORY AND THE NATURE OF SOLIDS - ACTIVITY 5420

1. Occurrence and Magnetic Behavior of Cr₃O-Type and Sigma Phases (M. V. Nevitt)

Magnetic Measurements: Construction of a cryostat for the measurement of paramagnetic susceptibilities and ferromagnetic saturation moments has been completed. Measuring circuits and other instrumentation are in final stages of completion, and the cryostat has been installed in the magnet in preparation for preliminary testing.

Ordering in Sigma: The study of the sigma phase has been extended to an investigation of the extent of ordering by X-ray diffraction methods. Atomic concentrations in the five types of lattice sites in the sigma phase will be deduced from observed line intensities using AVIDAC solutions of simultaneous structure factor equations. Preliminary work to determine the suitability of certain lines in the sigma pattern and to program the data for AVIDAC has been completed.

Ti₂Ni-Type Phases: The survey of binary transition metal systems for Cr₃O-type structures has resulted in the discovery of a family of phases, previously unreported, that are isostructural with Ti₂Ni. Lattice parameters for three of these complex cubic phases, all containing hafnium, are given in Table VII. Preliminary evidence has been obtained that this phase is also stable in certain of the systems of zirconium and titanium with the same element, although many of these do not appear to adhere to the A₂B stoichiometry. Work is now in progress to determine the composition ranges of stability and the lattice parameters for these isomorphs.

TABLE VII

New Ti ₂ Ni-Type Phases	
System	a ₀ , Angstroms
Hf - 30 Rh	12.326 ± 0.0002
Hf - 30 Ir	12.352 ± 0.0009
Hf - 30 Pt	12.461 ± 0.0009

2. The Hexagonal Phase Found in Certain Zirconium and Titanium Alloys (M. H. Mueller, L. Heaton)

The delta phase found in the U-Zr binary system and the omega phases formed in titanium alloys, with the beta-stabilizing elements, are characterized by being hard, brittle phases when compared to the body-centered structure from which they are derived. The delta phase of the U-Zr system is believed to be a stable phase, whereas the omega phase is unstable.

Earlier work indicated these phases to have a large, cubic unit cell formed by a tripling of the small body-centered cell. More recently, however, it has been found that the true unit cell is hexagonal, with three atoms per unit cell. The "c" axis of the hexagonal cell is along the [111] cubic direction and the "a" axis along the [110] cubic direction.

It is evident from X-ray rotation patterns, if the hexagonal is the true unit cell, that the hexagonal cells are symmetrically oriented so as to show cubic symmetry. These hexagonal cells may be regarded as derived from a twinning of the cubic cell; hence the cubic symmetry may be described as twin symmetry and not crystal symmetry.

The three atoms of the hexagonal unit cell are located in the following positions:

1 atom at (0, 0, 0)

1 atom at ($2/3$, $1/3$, $1/2$)

1 atom at ($1/3$, $2/3$, $1/2$)

Intensities of both powder patterns and single-crystal patterns indicate that the UZr_4 delta phase is at least somewhat ordered: zirconium atoms occupy the (0, 0, 0) positions and the remaining uranium and zirconium atoms are located at random in the two positions where Z is equal to $1/2$. This results in a layer-type structure with alternate layers of zirconium atoms (A-layer) arranged in an hexagonal array and a mixed uranium and zirconium layer (B-layer) with a six-membered ring arrangement. The ratio of uranium to zirconium atoms may vary in the B-layer, which accounts for the spread of the delta phase from approximately UZr_2 to UZr_4 . An attempt is being made with neutron diffraction to determine if the arrangement of titanium and vanadium atoms is similar in the omega phase.