Tech. Inf. Files

BNWL-378

/-

AEC
RESEARCH
and
DEVELOPMENT
REPORT

**QUARTERLY PROGRESS REPORT
A STUDY OF TUNGSTEN-TECHNETIUM ALLOYS
JANUARY 1, 1966-APRIL 1, 1966**

R. S. KEMPER

D. P. O'KEEFE

MARCH, 1967

BATTELLE-NORTHWEST

BATTELLE MEMORIAL INSTITUTE / PACIFIC NORTHWEST LABORATORY

LEGAL NOTICE

This report was prepared as an account of Government sponsored work. Neither the United States, nor the Commission, nor any person acting on behalf of the Commission:

A. Makes any warranty or representation, expressed or implied, with respect to the accuracy, completeness, or usefulness of the information contained in this report, or that the use of any information, apparatus, method, or process disclosed in this report may not infringe privately owned rights; or

B. Assumes any liabilities with respect to the use of, or for damages resulting from the use of any information, apparatus, method, or process disclosed in this report.

As used in the above, "person acting on behalf of the Commission" includes any employee or contractor of the Commission, or employee of such contractor, to the extent that such employee or contractor of the Commission, or employee of such contractor prepares, disseminates, or provides access to, any information pursuant to his employment or contract with the Commission, or his employment with such contractor.

PACIFIC NORTHWEST LABORATORY

RICHLAND, WASHINGTON

operated by

BATTELLE MEMORIAL INSTITUTE

for the

UNITED STATES ATOMIC ENERGY COMMISSION UNDER CONTRACT AT(45-1)-1830

PRINTED BY/ FOR THE U. S. ATOMIC ENERGY COMMISSION

3 3679 00060 5412

BNWL-378
UC-25, Metals, Ceramics,
and Materials

QUARTERLY PROGRESS REPORT
A STUDY OF TUNGSTEN-TECHNETIUM ALLOYS
JANUARY 1, 1966-APRIL 1, 1966

By

R. S. Kemper
D. P. O'Keefe
Metallurgy Department

March 1967

FIRST UNRESTRICTED
DISTRIBUTION MADE MAR 28 '67

Sponsored by the National Aeronautics and Space Administration
Project Management at Washington, D. C.
J. W. Maltz, Office of Advanced Research and Technology

PACIFIC NORTHWEST LABORATORY
RICHLAND, WASHINGTON

Printed in the United States of America
Available from
Clearinghouse for Federal Scientific and Technical Information
National Bureau of Standards, U.S. Department of Commerce
Springfield, Virginia 22151
Price: Printed Copy \$3.00; Microfiche \$0.65

Previous Quarterly Progress Reports in this series:

HW-83550	April 1, 1964-July 1, 1964
HW-84309	July 1, 1964-October 1, 1964
HW-84550	October 1, 1964-January 1, 1965
BNWL-141	January 1, 1965-April 1, 1965
BNWL-142	April 1, 1965-July 1, 1965
BNWL-162	July 1, 1965-October 1, 1965
BNWL-196	October 1, 1965-January 1, 1966

QUARTERLY PROGRESS REPORT
A STUDY OF TUNGSTEN-TECHNETIUM ALLOYS
JANUARY 1, 1966-APRIL 1, 1966

R. S. Kemper
D. P. O'Keefe

INTRODUCTION

Technetium is a sister element to rhenium and has many properties that are similar to rhenium. It is predicted that technetium will have about the same effects on tungsten as rhenium in regard to increase in workability, lowered ductile-to-brittle transition temperature, and improved ductility.

The objectives of the current work are to recover technetium from fission product wastes at Hanford and reduce to purified metal; prepare W-Tc alloys containing up to 50 at.% Tc; fabricate the alloy ingots to sheet stock, assessing the effect of technetium on workability; and perform metallurgical and mechanical property evaluation of the fabricated alloys.

Previous reports have described the separation and purification of 800 g of technetium metal powder, melting of technetium and W-Tc alloys, and some properties of the arc cast alloys.

CURRENT PROGRESS

TEST METHOD DEVELOPMENT

The first fabricated alloys of W-Tc will be in the form of small sheet specimens varying in thickness between 0.020 and 0.050 in. The initial mechanical properties testing to be done on these alloys will be to determine the effect of technetium content on the ductile-brittle transition temperature. A test method is being sought which can be used for

determining this parameter on a very small amount of material. For this purpose a bend test fixture, as shown in Figure 1, has been built. When this fixture is mounted in a test machine, a 3/4 in. long specimen can be loaded as a simple beam. Temperature control is provided with a circulating air oven.

Tests on pure tungsten have shown that the onset of cracking in the bend test specimen is usually adequately indicated by a drop in the test machine load indication. Some specimens of highly wrought tungsten, however, tend to exfoliate, and transverse cracking does not progress far enough in one step to give a clear indication on the load measuring system. Also, it is difficult to fit this type of specimen back together to determine bend angle at the initiation of failure. Therefore, a telescope was built to allow visual sighting of the first crack which in this test appears on the top surface of the specimen. The telescope, shown in Figure 2, provides about 15X magnification at a 12 in. distance.

Ductile-brittle transition data for pure tungsten specimens obtained in the process of evaluating the test method are shown in Figure 3. These data were obtained from bend specimen 3/4 x 1/4 in.

The main thing that remains to be done to implement this test method is to establish a procedure for defining the permanent set before fracture in terms of bend angle and thickness.

Neg 0661006-4

FIGURE 1. Bend Test Fixture on Instron Test Machine

Neg 0661006-1

FIGURE 2. *Sighting Telescope for Bend Test*

FIGURE 3. Ductile-Brittle Transition Temperatures for Tungsten Sheet Determined by Bend Test. Data points indicate the total deflection imparted to a simple beam to cause fracture.

DISTRIBUTIONNo. of
Copies

1	<u>Army Materials Research Agency</u> S. V. Arnold
2	<u>Atomic Energy Commission, Washington</u> Division of Reactor Development and Technology K. Horton
2	<u>Battelle Memorial Institute</u> Defense Metals Information Center R. I. Jaffee
3	<u>Bureau of Mines</u> Department of Interior Washington, D.C. R. F. Stevens, Jr., (Commodity Specialist)
1	<u>Bureau of Naval Weapons</u> Department of Navy Washington, D.C. 20546 T. F. Kearns, (RRMA-2)
1	<u>Chicago Patent Group</u>
1	<u>Climax Molybdenum Company of Michigan</u> 14419 Woodrow Wilson Detroit 38, Michigan M. Semchyschen
277	<u>Division of Technical Information Extension</u>
1	<u>General Electric Company</u> Research Laboratory P. O. Box 1088 Schenectady, New York
4	<u>General Electric Company, Cincinnati</u> L. P. Jahnke (Advanced Engine Technology Dept.) J. A. McGurty E. D. Sayre, (APED) C. S. Wukusick

No. of
Copies

1	<u>General Electric Company</u> ✓
Lamp Metal Component Department
Cleveland, Ohio
J. H. Keeler
1	<u>General Electric Company, Richland</u>
GETA File Copy
1	<u>General Telephone and Electronics Laboratories, Inc.</u>
Bayside 60, New York
L. L. Seigle
1	<u>Jet Propulsion Laboratory</u>
Engineering Mechanics Division
H. Martens
1	<u>Lawrence Radiation Laboratory</u>
J. Hadley
1	<u>NASA Ames Research Center</u>
Vehicle Environment Division
Charles A. Hermach
1	<u>NASA Goddard Space Flight Center</u>
Spacecraft Systems Division
H. E. Frankel
1	<u>NASA Langley Research Center</u>
Structures Research Division
E. E. Mathauser
2	<u>NASA Lewis Research Center</u>
W. D. Klopp, (105-1)
N. Saunders, (M&S Div)
1	<u>NASA Manned Spacecraft Center</u>
R. L. Johnston, (S&M Div)

No. of
Copies

- 1 NASA Marshall Space Flight Center
 W. R. Lucas, (R-P&VE-M)
- 2 National Aeronautics and Space Administration
 600 Independence Avenue S.W.
 Washington, D.C. 20546
 Joseph Maltz, (Code RRM)
- 2 National Aeronautics and Space Administration
 Universal North Building
 Washington, D.C. 20546
 Office of Grants & Research Contracts,
 (Code SC)
- 3 Richland Operations Office
 C. L. Robinson
 R. K. Sharp
 Technical Information Library
- 1 Union Carbide Corporation (ORNL)
 Metals and Ceramics
 M. L. Picklesimer
- 1 Universal-Cyclops Steel Corporation
 Bridgeville, Pennsylvania
 C. P. Mueller
- 1 Westinghouse Electric Corporation
 Research Laboratory
 Churchill Boro
 Pittsburgh 35, Pennsylvania
 J. H. Bechtold
- 1 Wright-Patterson Air Force Base
 Dayton, Ohio
 Materials Laboratory
 K. Elbaum

No. of
Copies

32

Battelle-Northwest

F. W. Albaugh
S. H. Bush
J. J. Cadwell
D. R. de Halas
L. A. Hartcorn
R. N. Johnson
R. S. Kemper
G. A. Last
J. E. Minor (10)
R. L. Moore
D. P. O'Keefe
F. P. Roberts
M. T. Walling
O. J. Wick (2)
F. W. Woodfield
Technical Information Files (5)
Technical Publications (2)