UNCLASSIFIED

X-822

OAK RIDGE NATIONAL LABORATORY

Operated By

UNION CARBIDE NUCLEAR COMPANY

UIC

POST OFFICE BOX P
OAK RIDGE, TENNESSEE

ORNL
CENTRAL FILES NUMBER

CF- 56-10-36

External Transmittal
Authorized
COPY NO. 36

DATE: October 8, 1956
SUBJECT: Alloys and Compounds of Niobium
TO: Listed Distribution
FROM: John P. Page

This memo constitutes a compilation of data on niobium and its compounds and alloys as reported in the unclassified literature. It is hoped that this information will be of use for alloy-development and phase-identification purposes.

LEGAL NOTICE

This report was prepared as an account of Government sponsored work. Neither the United States, nor the Commission, nor any person acting on behalf of the Commission:

A. Makes any warranty or representation, express or implied, with respect to the accuracy, completeness, or usefulness of the information contained in this report, or that the use of any information, apparatus, method, or process disclosed in this report may not infringe privately owned rights; or

B. Assumes any liabilities with respect to the use of, or for damages resulting from the use of any information, apparatus, method, or process disclosed in this report.

As used in the above, "person acting on behalf of the Commission" includes any employee or contractor of the Commission to the extent that such employee or contractor prepares, handles or distributes, or provides access to, any information pursuant to his employment or contract with the Commission.

This document contains information of a preliminary nature and was prepared primarily for internal use at the Oak Ridge National Laboratory. It is subject to revision or correction and therefore does not represent a final report.

UNCLASSIFIED

993-1

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency Thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

DISCLAIMER

Portions of this document may be illegible in electronic image products. Images are produced from the best available original document.

I. ALLOYS AND COMPOUNDS OF NIOBIUM

The Hume-Rothery theory of solid solution stipulates that if the atomic diameters of the solvent and solute differ by less than 14%-15%, and if valency conditions are met, one can expect a tendency toward the formation of solid solution. Figure 1⁽¹⁾ presents the interatomic distances in the crystals of the elements. Horizontal lines have been drawn at values plus-and-minus 15% of the atomic diameter of niobium.

ALUMINUM

The compound $NbAl_3$ is reported⁽²⁾. "The equilibrium diagram is probably similar to aluminum-titanium"⁽³⁾.

BERYLLIUM

A two-phase microstructure is reported⁽⁴⁾ at 10 wt % niobium.

BORON

An excellent discussion of niobium borides can be found in Refractory Hard Metals⁽⁵⁾. The following phases have been reported and confirmed^(6,7): 1) the solid solution of boron in niobium, 2) NbB , 3) Nb_3B_4 , and 4) NbB_2 . Nb_3B and Nb_2B are also tentatively established⁽⁷⁾, and two phases stable at high temperatures⁽⁶⁾.

CARBON

Refractory Hard Metals⁽⁵⁾ is suggested for reference on this system. A hypothetical phase diagram is given, but has not been reproduced in the present memo as it is highly doubtful. The most recent work⁽⁸⁾ reports solid solution of carbon in niobium to approximately 0.26 wt % carbon, a phase based on Nb_2C extending from 2.5 to 4.0 wt %, and the NbC phase, which is stable from 7 to 11 wt % (pure NbC).

CHLORINE

The chloride of columbium is volatilized when purified hydrogen is passed over the heated chloride powder. A heated article in this atmosphere becomes plated with the metal⁽⁹⁾.

CHROMIUM

X-ray analysis⁽¹⁰⁾ shows the only intermetallic compound in this system to be NbCr₂.

COBALT

"In the niobium-cobalt system a cobalt-rich solid solution with 7% niobium forms a eutectic with Co₅Nb₂ (melting point 1500°C) at 1250°C, 21% niobium. At room temperature cobalt retains 4% niobium in solid solution. Alloys with 4-8% niobium can be precipitation-hardened⁽¹¹⁾."

Figure 2⁽¹²⁾ shows the system as described above.

The existence of the intermetallic compound Co₂Nb is reported⁽¹³⁾.

DEUTERIUM

See Hydrogen.

FLUORINE

The free energy of formation of NbF₅ is presented in Figure 9⁽²⁸⁾.

GERMANIUM

The compound NbGe₂ is reported to exist⁽¹³⁾.

HYDROGEN

Figure 3 presents the solubility of hydrogen in metallic niobium, as determined by Sieverts and Moritz⁽¹⁴⁾. They report identical results with deuterium, although diffusion rates were considerably less.

The limiting composition was considered to be NbH , although $\text{NbH}_{0.86}$ was the composition attained by slow cool to room temperature. A plot of log solubility against reciprocal temperature yielded -22.0 kcal/mole for the heat of solution of hydrogen in niobium. "Normally, fresh niobium metal shows no absorptive capacity for hydrogen at room temperature, but, if the niobium is activated by heating in hydrogen at a high temperature, then on cooling to room temperature in hydrogen, the metal will continue to absorb hydrogen slowly until a composition corresponding to $\text{NbH}_{0.86}$ is reached⁽¹⁵⁾."

"A study of the hydrogen reactions shows that the rate of reaction is a function of the square root of the pressure. This evidence indicates that the hydrogen is diffusing into the columbium lattice as atoms and the surface is essentially free of a hydride film. The hydrogen reaction product on columbium is stable in vacua of 10^{-6} mm of Hg to a temperature of 250°C . Above this temperature the reaction product decomposes. A high temperature reaction product is stable in vacua of the order of 10^{-6} mm of Hg⁽¹⁶⁾."

"Metallic Nb dissolves hydrogen up to $\text{NbH}_{0.10}$ (0.11 wt %) and causes a lattice expansion from $a = 3.303$ to $3.318 \text{ \AA}$. The heterogeneous region of the $\alpha + \beta$ phase extends from $\text{NbH}_{0.10}$ (0.11 wt %) to $\text{NbH}_{0.57}$ (0.30 wt %). In this region the β phase has a lattice constant of $3.405 \text{ \AA}$, but with higher hydrogen content the lattice constant rises to $3.442 \text{ \AA}$ at $\text{NbH}_{0.86}$ (0.46 wt %)⁽¹⁷⁾."

IRIDIUM

The compound Nb_3Ir has been identified⁽¹⁸⁾.

IRON

The phase diagram⁽¹⁹⁾ for the iron-niobium system (to 70 wt % Nb) is presented in Figure 4, and the iron-rich end in Figure 5. NbFe_2 has been identified⁽²⁰⁾.

MANGANESE

The existence of Mn_2Nb has been established⁽²⁰⁾.

MOLYBDENUM

Molybdenum forms a continuous series of solid solutions with niobium⁽²¹⁾.

See Ternary Systems.

NICKEL

The niobium-nickel diagram⁽¹⁹⁾ to 60% niobium is presented in Figure 6. The solubility limit of the alpha phase may be somewhat higher than shown in the diagram.

NITROGEN

The solubility of nitrogen in niobium, as determined by Ang and Wert⁽²²⁾, is presented in Figure 7. The data were obtained by internal friction techniques. They state that "quench aging of supersaturated solid solutions of nitrogen in niobium takes place in reasonable times in the temperature range 300° to 500°C. Changes in internal friction, hardness, and electrical resistivity are found to accompany this change." The heat of solution was determined to be 4500 cal/mole.

"The reactions of niobium with nitrogen (were) studied over the temperature range of 500° to 800°C. The parabolic rate law may be fitted to the data. Using the method of Van Lempt, the parabolic rate law may be deduced from direct diffusion of nitrogen into the metal. The reactions are not taking place directly on the base, metal, but rather through a film of nitride which limits the pressure from exerting its normal influence on this type of reaction. The nitride film thickness is governed by the rate of formation and the rate

of solution. The reaction products are stable to the highest temperature tested, namely 923°C .⁽¹⁶⁾

The heat of activation of diffusion of nitrogen in niobium was determined⁽²³⁾ to be 38.6 Kcal/mole.

Brauer and Jander⁽²⁴⁾ investigated specimens in this system by X-ray methods. They found the following phases: 1) solid solution of nitrogen in niobium, extending to $\text{NbN}_{0.02}$ (0.03 wt %), 2) a hexagonal phase based on Nb_2N of which the single-phase region is $\text{NbN}_{0.4}$ to $\text{NbN}_{0.5}$ (3.5 to 4.5 wt %), 3) a tetragonal phase extending from $\text{NbN}_{0.75}$ to $\text{NbN}_{0.79}$ (8 to 9 wt %), and 4) three non-metallic phases. One of these is cubic and related to the tetragonal phase, with which it is in equilibrium from $\text{NbN}_{0.79}$ to $\text{NbN}_{0.89}$ (9 to 11 wt %). The other two phases are hexagonal. The system is non-metallic above $\text{NbN}_{0.89}$ (11 wt %).

OSMIUM

The intermetallic compound Nb_3Os is reported⁽¹⁸⁾.

OXYGEN

The solid solubility of oxygen in niobium was determined by Seybolt⁽²⁵⁾, and is presented in Figure 8.

Brauer⁽²⁶⁾ reports the existence of three oxides: NbO_2 , NbO , and Nb_2O_5 . The latter is reported to have three modifications: the low, or "T" form, stable to 900°C , the middle, or "M" form, stable from 1000° to 1100°C , and the high or "H" form, stable above 1100°C . The existence of these forms has been confirmed⁽²⁷⁾, although the temperature ranges of stability were questioned. The oxides were not found to be appreciably volatile at temperatures from 1000° to 1375°C . The free energies of formation of the three oxides

are presented in Figure 9⁽²⁸⁾. The pentoxide has a negative coefficient of thermal expansion between room temperature and 600°C, where it becomes positive⁽²⁹⁾.

The reaction kinetics were first studied systematically by Gulbransen and Andrew⁽¹⁶⁾. They found that a modified form of the parabolic rate law could be fitted to the data between 200° and 375°C. The effect of pressure was reported to be small.

Inouye⁽²⁷⁾ studied the scaling reaction in wet air ($p_{H_2O} = 18.6$ mm Hg), and dry air from 400° to 1200°C. At 400°C the oxidation rate is initially slow, but tends toward linearity after 21 hr. Essentially linear oxidation rates were determined at 600°, 700°, 800°, 900°, 1000°, and 1200°C. An Arrhenius plot of reaction rate versus reciprocal temperature showed an inflection at 900°C, at which temperature the pentoxide changes form.

Recent work by Bridges and Fassell⁽³⁰⁾ indicates that niobium oxidizes according to the linear rate law from 400° to 800°C, and that the oxidation rate is pressure-sensitive above 550°C (especially between 550° and 650°C). "Theoretical considerations indicate that an equilibrium adsorption process occurs prior to the rate-determining step."

PHOSPHORUS

"NbP₂ decomposes to NbP at 650°C in vacuo; NbP is dimorphous like TaP⁽³¹⁾."

PLATINUM

The existence of the compound Nb₃Pt is reported⁽¹⁸⁾.

SILICON

The niobium-silicon diagram, as determined by Knapton,⁽³²⁾ is reported in Figure 10.

SULFUR

"The (hexagonal) NbS phase was stable in the presence of excess S, but formed a WC-structure at low S contents⁽³³⁾."

TANTALUM

Tantalum forms a continuous series of solid solutions with niobium⁽²¹⁾.

See Ternary Systems.

THORIUM

The phase diagram⁽³⁴⁾ for the niobium-thorium system is presented in Figure 11.

TIN

The existence of the compound Nb_3Sn is reported⁽¹⁸⁾; this compound has a supraconductivity transition temperature of 18.05°K , the highest known. " Nb_3Sn (is) formed by a peritectic reaction between the respective metals at a temperature between 1200° and 1500°C ⁽³⁵⁾."

TITANIUM

The phase diagram⁽³⁶⁾ for the niobium-titanium system is presented in Figure 12.

TUNGSTEN

Tungsten forms a continuous series of solid solutions with niobium⁽²¹⁾.

See Ternary Systems.

URANIUM

The phase diagram⁽³⁴⁾ for the niobium-uranium system is presented in Figure 13.

VANADIUM

The phase diagram⁽³⁷⁾ for the niobium-vanadium system is presented in Figure 14.

ZIRCONIUM

The phase diagram⁽³⁸⁾ for the niobium-zirconium system is presented in Figure 15.

TERNARY SYSTEMS

Lattice parameter measurements for alloys of tungsten, molybdenum, and tantalum, with each other, and with niobium were made by Buckle⁽²¹⁾. The results of this investigation are presented in Figures 16 and 17.

II. X-RAY AND CRYSTALLOGRAPHIC DATA

NIOBIUM

Structure: body-centered cubic

Lattice Constant: $a = 3.3008 \text{ \AA}$ at 20°C Transformations: none to melting point, 2415°C COMPOUNDS

REFERENCE

ALUMINUM

NbAl_3 : tetragonal; $a = 5.427 \text{ \AA}$, $c = 8.584 \text{ \AA}$	2
---	---

BORON

"Best" values given

NbB_2 : hexagonal (C-32); $a = 3.09 \text{ \AA}$, $c = 3.30 \text{ \AA}$ decomposes at $T > 2,900^\circ\text{C}$	5, 6, 7
---	---------

Nb_3B_4 : orthorhombic (D-76); $a = 3.31 \text{ \AA}$, $b = 14.08 \text{ \AA}$, $c = 3.14 \text{ \AA}$	5, 6, 7
--	---------

NbB : orthorhombic (Bf); $a = 3.30 \text{ \AA}$, $b = 8.72 \text{ \AA}$, $c = 3.17 \text{ \AA}$	5, 6, 7
--	---------

Nb_9B : cubic; $a = 4.21$ ($T > 800^\circ\text{C}$)	13
---	----

CARBON

NbC : cubic (B1); $a = 4.461 \text{ \AA}$, density = $7.56\text{--}7.85 \text{ g/cm}^3$ hardness 2,400-2,700 VEN, melting point; $3,500^\circ\text{C}$	5, 8
---	------

$\text{NbC/Nb}_4\text{C}_3$: lines: 2.56, 2.22, 1.57 intensity: 100, 100, 100	39
---	----

$a = \sim 4.40 \text{ \AA}$	13
-----------------------------	----

Nb_2C : hexagonal close-packed, $a = 3.111\text{--}3.120 \text{ \AA}$, $c = 4.944\text{--}4.948 \text{ \AA}$	8
---	---

CHROMIUM

REFERENCE

NbCr₂: face-centered cubic (C-15); 24 atoms/unit cell
 Interatomic distances: Nb-Cr, 2.897 Å
 Nb-Nb, 3.027 Å
 Cr-Cr, 2.471 Å

10

$a = 6.98 \text{ Å}$

13

Lines: 2.10, 2.46, 1.34
 intensity: 100, 75, 75

39

COBALT

Nb_{0.8}Co_{2.2}: C-36 type; $a = 4.73 \text{ Å}$, $c = 14.43 \text{ Å}$
 $a = 4.729 \text{ Å}$, $c = 15.39 \text{ Å}$

13

11

NbCo₂: C-15 type; $a = 6.75 \text{ Å}$

11, 13

GERMANIUM

NbGe₂: C-40 type; $a = 4.96 \text{ Å}$, $c = 6.77 \text{ Å}$

13

HYDROGEN

Nb to NbH_{0.10}: lattice expansion from 3.303 Å to 3.318 Å

17

NbH_{0.10} to NbH_{0.57}: hydride lattice constant, $a = 3.405 \text{ Å}$

17

NbH_{0.86}: $a = 3.442 \text{ Å}$

17

IRIDIUM

Nb₃Ir: A-15 type; $a = 5.131 \text{ Å}$, density = 11.52 g/cm³

18

IRON

NbFe₂: MgZn₂ (C-14) type; $a = 4.82 \text{ Å}$, $c = 7.87 \text{ Å}$

13, 20

MANGANESE

Mn₂Nb: MgZn₂ (C-14) type; $a = 4.87 \text{ Å}$, $c = 7.96 \text{ Å}$

13, 20

MOLYBDENUM

Solid Solution, See Figures 16 and 17.

21

NICKEL

NbNi₃: A-3 type (deformed)

13

NITROGEN

NbN: three phases determined by Brauer

24

- 1) B-1 type; $a = 4.38 \text{ \AA}$
- 2) hexagonal; $a = 2.93 \text{ \AA}$, $c = 5.45 \text{ \AA}$
- 3) hexagonal; $a = 2.95 \text{ \AA}$, $c = 11.25 \text{ \AA}$

NbN: lines: 1.30, 1.02, 1.87 also 2.57, 2.20, 1.56
 intensity: 100, 100, 90 100, 100, 75

39

NbN: NaCl type; $a = 4.38 \text{ \AA}$

40

NbN_{0.80-0.90}: hexagonal; $a = 2.94 \text{ \AA}$, $c = 2.79 \text{ \AA}$

33

NbN_{0.75} (approx): tetragonal; $a = 4.38 \text{ \AA}$, $c = 4.31 \text{ \AA}$

13

NbN_{0.75}: lines: 2.49, 1.53, 1.32
 intensity: 100, 80, 60

39

Nb₂N (approx): L₃-type; lattice constants $3.05 \text{ \AA}$ and $4.96 \text{ \AA}$

13

OSMIUM

Nb₃Os: A-15 type structure; $a = 5.12 \text{ \AA}$, density 11.59 g/cm^3

18

OXYGEN

Nb₂O₅: lines: 3.17, 4.04, 2.48 and 3.93, 3.14, 2.45
 intensity: 100, 100, 80 100, 100, 70

39

Nb₂O₅: pseudohexagonal orthorhombic $a_1 = 6.16 \text{ \AA}$ $a_2 = 3.65 \text{ \AA}$ $a_3 = 3.94 \text{ \AA}$

27

Nb₂O₅ (high temp): lines: 3.75, 3.65, 3.49
 intensity: 100, 100, 100

39

NbO: face-centered cubic; $a = 4.20 \text{ \AA}$

27

NbO₂: rutile structure; $a = 4.84 \text{ \AA}$, $c = 2.99 \text{ \AA}$, $c/a = 0.618$

27

Solid solution: lattice expansion to $3.313 \text{ \AA}$ at 0.7 wt % oxygen

25

REFERENCE

PLATINUM

Nb_3Pt : A-15 type structure; $a = 5.153 \text{ \AA}$, density 11.50 g/cm^3 18

SILICON

NbSi_2 : C-40 type structure; $a = 4.285 \text{ \AA}$, $c = 6.576 \text{ \AA}$, density 5.29 g/cm^3
hardness = 1,050 VHN, melting point = $1,950^\circ - 2,000^\circ\text{C}$ 5

SULFUR

NbS : hexagonal; $a = 3.32 \text{ \AA}$, $c = 6.46 \text{ \AA}$, $c/a = 1.95$ 33

TANTALUM

: Continuous solid solution, see Figures 16 and 17. 21

TIN

Nb_3Sn : A-15 structure; $a = 5.276 \text{ \AA}$, density 8.92 g/cm^3 18

TUNGSTEN

Continuous solid solution, see Figures 16 and 17 21

923-13

COMPLEX NIOBATES (REFERENCE 39)

	<u>Lines and Intensities</u>		
$K_2O \cdot Nb_2O_5$	2.83 100	2.00 100	1.64 100
$Na_2O \cdot Nb_2O_5$	2.75 100	1.95 100	1.74 100
$(Fe, Mn)O \cdot (Nb, Ta)_2O_5$	3.00 100	1.72 100 and 3.33 80	1.45 100 2.57 80
$FeO \cdot Nb_2O_5$	2.92 100	1.69 100	1.44 90
$FeO \cdot (Nb, Ta)_2O_5 \cdot 5TiO_2$	1.70 100	3.27 70	2.50 50
$3Al_2O_3 \cdot 2Ta_2O_5 (Nb_2O_5)$	1.64 100	1.39 96	1.02 91
$NbO \cdot PO_4$	3.45 100	3.20 100	1.88 100
$NaCaNb_2PO_6 ?$	1.84 100	1.57 100	0.88 100

REFERENCES

- 1) Begley, R. T., and Fredenburg, M. S., "Development of Niobium Base Alloys," Westinghouse (Report A-2173, April, 1956).
- 2) Brauer, G., Naturwiss., 26, 710 (1938).
- 3) Mondolfo, L. F., Metallography of Aluminum Alloys, Wiley and Sons, New York (1943).
- 4) Kaufmann, A. R., Gordon, P., Lillie, D. W., "The Metallurgy of Beryllium," Trans. ASM, 42, 785-844 (1950).
- 5) Schwarzkopf, P., and Kieffer, R., Refractory Hard Metals, Macmillan, New York (1953).
- 6) Anderson, L. H., Kiessling, R., "Investigations on the Binary Systems of Boron with Chromium, Columbium, Nickel, and Thorium," Acta. Chem. Scand., 4, 160-164 (1950).
- 7) Brewer, C., Sawyer, D. L., Templeton, D. H., and Dauben, C. H., "A Study of Refractory Borides," USAE Report No. UCRL-610, Feb. 24, 1950).
- 8) Brauer, G., Renner, H., and Wernet, J., "The Carbides of Niobium," Z. Anorg. Chem., 27, 249-267 (1954) (In German) Metallurgical Abstracts, 33, 293 (1955).
- 9) Powell, Campbell, and Gonser, J. Electrochem. Soc., 93, 258-265 (1948).
- 10) Duwez, P., and Martens, H., "Crystal Structure of $TaCr_2$ and $NbCr_2$," J. Metals, 4, 72-74 (1952).
- 11) Koster, W., and Mulfinger, W., "The Systems of Cobalt with Boron, Arsenic, Zirconium, Niobium, and Tantalum," Z. Metallkunde, 30, 348-350 (1938) (In German) Metallurgical Abstracts, 5, 578 (1938).
- 12) Reprinted from: Myers, R. H., "The Constitution and Properties of Alloys Containing Tantalum and Columbium," Metallurgia, 39, 57-62 (Dec., 1948).
- 13) Smithells, C. J., Metals Reference Book, Vol. I, pp. 193-211, Interscience, New York, 1955.
- 14) Sieverts, A., and Moritz, H., "Niobium and Hydrogen, Niobium and Deuterium," Z. Anorg. Chem., 247, 124-130 (1941) (In German).
- 15) Hurd, D. T., An Introduction to the Chemistry of the Hydrides, Wiley and Sons, New York (1952).

- 16) Gulbranson, E. A., and Andrew, K. F., "Kinetics of the Reactions of Columbium and Tantalum with Oxygen, Nitrogen, and Hydrogen," Trans. AIME, 188, 586-599 (1950).
- 17) Trzebiatowski, W., and Stalinski, B., "Magnetic Susceptibilities of Niobium Hydrides," Bull. Acad. Polon. Sci., 1, (7), 317-318 (1953) (111) (Russian); Metallurgical Abstracts, 22, 14 (1954).
- 18) Geller, S., Matthias, T., and Goldstein, R., "Some New Intermetallic Compounds with the Beta-Wolfram Structure," J. Amer. Chem. Soc., 77, 1502-1504 (1955).
- 19) Reprinted from Metals Handbook, American Society for Metals, 1948 ed.
- 20) Wallbaum, H. J., X-ray Examination of the Structure of Alloys of Composition AB_2 of the Iron Group of Metals with Titanium, Zirconium, Niobium and Tantalum," Z. Krist., 103, 391-402 (1941) (In German).
- 21) Buckle, H., "Structure and Microhardness of Binary and Ternary Systems of the Metals Columbium, Tantalum, Molybdenum, and Tungsten," Metallforsch., 1, 53 (1946) (In German).
- 22) Ang, C. Y., and Wert, C., "Some Properties of Columbium Containing Nitrogen," J. Metals, 5, 1032-1036 (1953).
- 23) Ang, C. Y., "Activation Energies and Diffusion Coefficients of Oxygen and Nitrogen in Niobium and Tantalum," Acta. Met., 1, 123 (1953).
- 24) Brauer, G., and Jander, J., "The Nitrides of Niobium," Z. Anorg. Chem., 270, 160-178, (1952) (In German) Metallurgical Abstracts, 21, 429 (1954).
- 25) Seybolt, A. U., "Solid Solubility of Oxygen in Niobium," J. Metals, 6, 774-776, (1954).
- 26) Brauer, G., "The Oxides of Niobium," Z. Anorg. Chem., 248, 1, (1941) (In German).
- 27) Inouye, H., "Scaling of Columbium in Air," USAEC Report No. ORNL-1565, September 1, 1953.
- 28) Glassner, A., "A Survey of the Free Energies of Formation of the Fluorides, Chlorides, and Oxides of the Elements to 2500°K," USAEC Report No. ANL-5107, (1953).
- 29) Durbin, E. A., and Harman, C. G., "An Appraisal of the Sintering Behavior and Thermal Expansion of Some Columbates," USAEC Report No. BMI-791, December 15, 1952.
- 30) Bridges, D. W., and Fassell, W. M., Jr., "High Pressure Oxidation of Niobium," J. Electrochem. Soc., 103, 326-330 (1956).

573-12

- 31) Zambusch, M., et al., "System Niobium-Phosphorus," Z. Anorg. Chem., 249, 14-20 (1942). (In German).
- 32) Knapton, A. G., "The System Niobium-Silicon and the Effect of Carbon on the Structure of Certain Silicides," Nature, 175, 730 (1955).
- 33) Schonberg, N., "The Tungsten Carbide and Nickel Arsenide Structures," Acta. Met., 2, 427-432 (1954) Metallurgical Abstracts, 22, 196 (1954).
- 34) Saller, H. A., and Rough, F. A., "Compilation of US and UK Uranium and Thorium Constitutional Diagram," USAEC Report No. EMI-1000, June 1, 1955.
- 35) Matthias, B. T., et al., "Superconductivity of Nb_3Sn ," Phys. Rev., 92, 1954 (1954) Metallurgical Abstracts, 22, 532 (1955).
- 36) Hansen, M., et al., "Systems Titanium-Molybdenum and Titanium-Columbium," J. Metals, 3, 881-888 (1951).
- 37) Wilhelm, H. A., Carlson, O. N., and Dickenson, J. M., "Columbium-Vanadium Alloy System," Trans. AIME, 200, 915-918 (1954).
- 38) Rogers, B. A., and Atkins, D. F., "The Zirconium-Columbium Diagram," USAEC Report No. ISC-500, June 29, 1954.
- 39) Cumulative Alphabetical and Grouped Numerical Index of X-ray Diffraction Data; American Society for Testing Materials, 1955.
- 40) Duwez, P., and Odell, F., "Phase Relationships in the Binary Systems of Nitrides and Carbides of Zirconium, Niobium, Titanium, and Vanadium," J. Electrochem. Soc., 97, 299-304 (1950).

FIGURE 1

FIGURE 2

553- 18

Solubility of Hydrogen in Niobium

FIGURE 3

Niobium-Iron

FIGURE 4

Niobium-Iron

FIGURE 5

Niobium-Nickel
 FIGURE 6

UNCLASSIFIED
 ORNL-LR-DWG 12485

Solid Solubility of Nitrogen in Niobium
 FIGURE 7

Solubility of Oxygen in Solid Niobium

FIGURE 8

Free Energies of Formation of NbF_5 , NbO , NbO_2 , and Nb_2O_5

FIGURE 9

Silicon-Niobium
FIGURE 10

UNCLASSIFIED
ORNL-LR-090 12485

Niobium-Thorium
FIGURE 11

UNCLASSIFIED
ORNL-48-076 (2535)

Niobium - Titanium

FIGURE 12

UNCLASSIFIED
ORNL-48-076 (2535)

Niobium - Titanium

FIGURE 13

Niobium - Vanadium.

FIGURE 14

Niobium - Zirconium

FIGURE 15

FIGURE 16

FIGURE 17

1-26