ANL-5603
Chemistry

ARGONNE NATIONAL LABORATORY
P. O. Box 299
Lemont, Illinois

THE HEAT CAPACITY AND THERMODYNAMIC FUNCTIONS
OF TETRAURANIUM NONOXIDE FROM 5 TO 310°K

by

Darrell W. Osborne, Edgar F. Westrum, Jr., and Harold R. Lohr

August, 1956

Operated by The University of Chicago
under
Contract W-31-109-eng-38

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency Thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

DISCLAIMER

Portions of this document may be illegible in electronic image products. Images are produced from the best available original document.

2

THE HEAT CAPACITY AND THERMODYNAMIC FUNCTIONS OF TETRAURANIUM NONOXIDE FROM 5 TO 310°K

Darrell W. Osborne, Edgar F. Westrum, Jr.,¹ and Harold R. Lohr²

Abstract

The heat capacity of U_4O_9 was measured from 5 to 310°K; from these data the entropy, enthalpy, and free energy function were calculated. At 298.16°K., the values of C_p , S° , $(H^\circ - H_0^\circ)/T$, and $(F^\circ - H_0^\circ)/T$ are 70.11 ± 0.07 , 80.29 ± 0.08 , 40.69 ± 0.04 , and 39.60 ± 0.04 cal deg⁻¹ mole⁻¹, respectively. In contrast to the behavior of UO_2 , there is no anomaly in the heat capacity of U_4O_9 in the temperature range investigated.

Measurements of the low temperature heat capacities of actinide compounds provide useful thermodynamic data and may afford information concerning the electronic interactions in these substances. In UO_2 ³ and in NpO_2 ⁴ lambda-type anomalies have been observed near 30°K; these have been interpreted^{3,4,5,6} as arising from an antiferromagnetic ordering of the magnetic moments of the cations at lower temperatures.

Uranium dioxide absorbs oxygen at room temperature, forming non-stoichiometric oxides which disproportionate at higher temperatures into phases of compositions given by the formulas U_4O_9 and either $\text{UO}_2 + x$ or $\text{U}_3\text{O}_8 - x$.⁷ The structures of U_4O_9 and UO_2 are very similar,^{7,8,9} the uranium cations in both being arranged in a face-centered cubic array. In U_4O_9 one oxygen anion is added, perhaps interstitially in the (1/2, 1/2, 1/2) position, to the four uranium cations and eight oxygen anions contained in each unit cell of UO_2 , and the lattice constant contracts about 1/2%. The similarity of the structures made it appear desirable to determine whether U_4O_9 has an anomaly in its heat capacity similar to that observed in UO_2

¹Department of Chemistry, University of Michigan, Ann Arbor, Michigan.

²Present Address: Augustana Theological Seminary, Rock Island, Illinois.

³W. M. Jones, J. Gordon and E. A. Long, J. Chem. Phys., 20, 695 (1952).

⁴E. F. Westrum, Jr., J. B. Hatcher and D. W. Osborne, J. Chem. Phys. 21, 419 (1953).

⁵D. W. Osborne, and E. F. Westrum, Jr., J. Chem. Phys. 21, 1884 (1953).

⁶A. Arrott and J. E. Goldman, Phys. Rev., 99, 1641 (1955).

⁷F. Grönvold, J. Inorg. Nuclear Chem., 1, 357 (1955).

⁸H. Héring and P. Pério, Bull. soc. chim. France, 351 (1952).

⁹J. S. Anderson, Bull. soc. chim. France, 781 (1953).

The U_4O_9 Sample. The calorimetric sample, which had to be of high purity, well-defined composition, and complete homogeneity, was prepared by Fredrik Grønvold of the University of Oslo. Essentially the same procedure as that recommended by Hönigschmid¹⁰ was used for the purification of uranium and the preparation of pure U_3O_8 . The U_3O_8 was reduced to UO_2 by heating it in alumina boats in a stream of anhydrous hydrogen at 500°C until the evolution of water ceased; the sample was then heated for an additional four hours at 1200°C . The material was cooled in the hydrogen atmosphere. Stoichiometric quantities of this UO_2 and of U_3O_8 prepared by oxidizing UO_2 to constant weight at 800°C were mixed and placed in quartz tubes, which were subsequently evacuated and sealed. The mixture was heated for seven days at 800°C and then gradually cooled to 20°C over a period of two months.

Gravimetric analyses by ignition to U_3O_8 gave $86.81 \pm 0.08\%$ uranium (theoretical, 86.86%). Determinations of uranium by cerate oxidimetry with weight burettes gave $87.04 \pm 0.1\%$. Dissolution of the sample in BrF_3 ¹¹ revealed an oxygen content of $13.14 \pm 0.02\%$ (theoretical, 13.14%). Spectrochemical analyses showed the presence of the following elements (in ppm): 10 Al, 0.2 B, 10 Cu, 7 Fe, 5 Mg, 1 Pb, and 70 Si. The following elements were not detected (the numbers indicate the sensitivity limit in ppm): 1 Ag, 10 As, 0.5 Be, 1 Bi, 20 Ca, 4 Ce, 5 Co, 1 Cr, 2 Dy, 0.8 Er, 0.2 Eu, 2 Gd, 4 Ho, 20 K, 0.4 La, 1 Li, 0.8 Lu, 1 Mn, 20 Mo, 2 Na, 4 Nd, 5 Ni, 50 P, 8 Pr, 1 Sb, 4 Sm, 5 Sn, 4 Tb, 20 Th, 50 Ti, 0.8 Tm, 0.1 Y, 0.4 Yb, and 50 Zn. Increased sensitivity of detection of rare earth elements was obtained by the extraction of the uranium into tributylphosphate and the subsequent spectroscopic examination of the raffinate by the copper spark method.¹²

Experimental Technique. The cryostat,⁴ calorimeter,⁵ and the adiabatic method of operation⁴ have been described previously. The calorimeter was loaded with the sample, evacuated and filled with helium gas at one atmosphere pressure and 300°K to improve the establishment of thermal equilibrium.

Temperatures were determined with a capsule-type platinum resistance thermometer (Laboratory designation A-1) contained in a central well in the calorimeter. It was calibrated on the temperature scale of the National Bureau of Standards¹³ from 14 to 373°K . Below 14°K the scale was obtained by fitting the equation $R = A + BT^2 + CT^5$ to the resistance at the boiling point of helium and to the resistance and dR/dT at 14°K . It is considered that the temperature scale reproduced the thermodynamic scale within 0.1° from 4 to 14°K , within 0.03° from 14 to 90°K , and within 0.05° above 90°K . The ice point was taken as 273.16°K .

¹⁰O. Hönigschmid, Z. anorg. allgem. Chem., 226, 289 (1936).

¹¹H. R. Hoekstra and J. J. Katz, Anal. Chem. 25, 1608 (1953).

¹²M. Fred, N. H. Nachtrieb, and F. S. Tomkins, J. Opt. Soc. Amer., 37, 279 (1947)

¹³H. J. Hoge and F. G. Brickwedde, J. Research Natl. Bur. Standards, 22 351 (1939).

4

Calibrated instruments were used in the determination of all the experimental quantities, including the time interval of the energy input. The heat capacity of the empty calorimeter was determined in a separate series of measurements.

Heat Capacity Results. The experimental heat capacity data are presented in chronological sequence in Table I. Corrections for the finite temperature increments employed (which can usually be inferred from the adjacent mean temperatures in Table I) and for slight differences in the amounts of helium and solder in the measurements on the empty and full calorimeter have been applied. The data are presented in terms of 1096.28 g of U_4O_9 and the defined thermochemical calorie of 4.1840 absolute joules. The calorimetric sample weighed 99.778 g (in vacuo).

No anomaly occurs in the heat capacity of U_4O_9 between 5° and 310°K, in contrast to the behavior of UO_2 . Although the geometric structures and interatomic distances of these two compounds are very similar, it appears that the electronic configurations are sufficiently different to modify the exchange interactions that give rise to the antiferromagnetic ordering and the thermal anomaly in UO_2 .

Thermodynamic Functions. The heat capacity read from a smooth curve through the experimental results and some thermodynamic functions computed from the heat capacity are presented at selected temperatures in Table II. The heat capacity values are considered to have a probable error of 0.1% above 25°K, 1% at 14°K, and about 5% at 5°K. Since the measured heat capacities are proportional to the temperature over the range of 5 to 9°K, a linear extrapolation was used below 5°K. It was assumed that no anomaly occurs in the heat capacity below 5°K. Nuclear spin and isotope mixing contributions are not included in the entropy and free energy functions. The estimated probable error in the thermodynamic functions is 0.1% above 100°K, provided that there is no anomaly below 5°K; the tabular values include more digits than are justified by the probable error in order to make the table internally consistent.

Acknowledgement. The authors acknowledge their appreciation to Fredrik Grønvold of Chemical Institute A of the University of Oslo, Norway, for his interest in this problem and for his preparation of the calorimetric sample. They thank R. W. Bane for the uranium assays, Dr. H. R. Hoekstra for the oxygen analysis, and J. P. Faris and J. A. Goleb for the spectrochemical analyses.

S

Table I

MOLAL HEAT CAPACITY OF U_4O_9 (in cal deg⁻¹mole⁻¹)

Mol. wt = 1096.28; 0°C = 273.16°K

T, °K	C _p	T, °K	C _p	T, °K	C _p
SERIES I		53.72	16.27	169.14	49.45
5.37	0.52	58.72	18.10	178.59	51.44
6.32	0.66	64.17	20.06	187.98	53.33
7.23	0.73	70.46	22.19	197.33	55.02
8.28	0.84	77.61	24.55	206.79	56.75
9.46	0.97	77.65	24.59	216.47	58.33
10.42	1.09	85.46	27.15	226.29	59.93
11.71	1.28	93.72	29.69	236.22	61.43
13.05	1.51	102.64	32.31	246.27	63.00
14.44	1.813	SERIES II		256.46	64.43
15.91	2.111	63.05	19.66	266.75	65.94
17.46	2.489	69.39	21.84	276.88	67.34
18.98	2.910	76.58	24.22	286.92	68.68
20.49	3.380	84.39	26.79	296.88	69.95
22.18	3.927	92.59	29.33	305.82	71.46
24.13	4.626	101.49	31.97	SERIES III	
26.62	5.558	111.14	34.78	9.28	0.93
29.57	6.699	120.91	37.53	10.65	1.10
32.76	8.002	130.54	40.16	11.98	1.31
36.29	9.447	140.24	42.69	13.26	1.56
40.09	11.00	150.01	45.09	14.56	1.830
44.28	12.65	159.70	47.36	15.99	2.132
48.90	14.45	169.27	49.50	17.53	2.505

6

Table II

THERMODYNAMIC PROPERTIES OF U_4O_9 AT SELECTED TEMPERATURES

T, °K	C_p , cal deg ⁻¹ mole ⁻¹	S^0 , cal deg ⁻¹ mole ⁻¹	$H^0 - H_0^0$, cal deg ⁻¹ mole ⁻¹	$\left(\frac{H^0 - H_0^0}{T}\right)$, cal deg ⁻¹ mole ⁻¹	$-\left(\frac{F^0 - H_0^0}{T}\right)$, cal deg ⁻¹ mole ⁻¹
5	0.50	0.50	1.25	0.25	0.25
10	1.02	1.00	5.01	0.50	0.50
15	1.913	1.569	12.16	0.811	0.758
20	3.224	2.285	24.79	1.240	1.045
25	4.946	3.183	45.07	1.803	1.380
30	6.869	4.253	74.5	2.485	1.768
35	8.919	5.466	114.0	3.258	2.208
40	10.96	6.790	163.7	4.093	2.697
45	12.93	8.196	223.5	4.966	3.230
50	14.87	9.659	293.0	5.860	3.799
60	18.57	12.700	460.3	7.672	5.028
70	22.00	15.826	663.6	9.480	6.346
80	25.36	18.986	900.6	11.257	7.729
90	28.55	22.160	1170.3	13.003	9.157
100	31.53	25.323	1470.8	14.708	10.615
110	34.45	28.465	1800.7	16.370	12.095
120	37.27	31.584	2159.3	17.994	13.590
130	40.02	34.677	2545.9	19.584	15.093
140	42.63	37.739	2959.2	21.138	16.601
150	45.09	40.765	3397.9	22.652	18.113
160	47.43	43.750	3860.5	24.128	19.622
170	49.66	46.693	4346.0	25.565	21.128
180	51.73	49.590	4853.0	26.961	22.629
190	53.72	52.441	5380.4	28.318	24.123
200	55.55	55.244	5926.8	29.634	25.610
210	57.27	57.996	6491.0	30.910	27.086
220	58.92	60.698	7072.0	32.145	28.553
230	60.52	63.353	7669.2	33.344	30.009
240	62.04	65.961	8282.0	34.508	31.453
250	63.52	68.524	8909.8	35.639	32.885
260	64.94	71.042	9552.0	36.739	34.303
270	66.39	73.520	10208.7	37.810	35.710
280	67.76	75.961	10879.5	38.855	37.106
290	69.08	78.361	11563.8	39.875	38.486
300	70.34	80.724	12260.9	40.870	39.854
273.16	66.82	74.29	10419	38.14	36.15
298.16	70.11 ± 0.07	80.29 ± 0.08	12132 ± 12	40.69 ± 0.04	39.60 ± 0.04