10
SEP 14 1967

UNCLASSIFIED

~~CONFIDENTIAL~~
GEMP-530

Classification cancelled (or changed to _____)

by authority of _____

by H.F.C. TIC, date SEP 21 1973

MASTER

Nuclear Materials & Propulsion Operation

SUMMARY REPORT- HIGH TEMPERATURE MATERIALS ENGINEERING PROPERTIES EVALUATIONS (TASK 57017)

J. B. Conway
W. L. McCullough

August 18, 1967

SPECIAL REREVIEW
FINAL
DETERMINATION
Class: U

Reviewers	Class.	Date
JRP	U	4-8-82

~~RESTRICTED DATA~~
~~GROUP 1~~
~~Excluded from automatic downgrading and declassification~~

UNCLASSIFIED

NUCLEAR TECHNOLOGY DEPARTMENT
NUCLEAR ENERGY DIVISION

GENERAL ELECTRIC

67 8841

~~CONFIDENTIAL~~
~~RESTRICTED DATA~~

THIS DOCUMENT CONTAINS RESTRICTED DATA AS DEFINED IN THE ATOMIC ENERGY ACT OF 1954. ITS TRANSMITTAL OR THE DISCLOSURE OF ITS CONTENTS IN ANY MANNER TO AN UNAUTHORIZED PERSON IS PROHIBITED.

GROUP 1

EXCLUDED FROM AUTOMATIC DOWNGRADING AND DECLASSIFICATION.

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency Thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

DISCLAIMER

Portions of this document may be illegible in electronic image products. Images are produced from the best available original document.

LEGAL NOTICE

This report was prepared as an account of Government sponsored work. Neither the United States, nor the Commission, nor any person acting on behalf of the Commission:

A. Makes any warranty or representation, expressed or implied, with respect to the accuracy, completeness, or usefulness of the information contained in this report, or that the use of any information, apparatus, material, method, or process disclosed in this report may not infringe privately owned rights; or

B. Assumes any liabilities with respect to the use of, or for damages resulting from the use of any information, apparatus, material, method, or process disclosed in this report.

As used in the above, "person acting on behalf of the Commission" includes any employee or contractor of the Commission, or employee of such contractor, to the extent that such employee or contractor of the Commission, or employee of such contractor prepares, disseminates, or provides access to, any information pursuant to his employment or contract with the Commission or his employment with such contractor.

Facsimile Price \$

Microfilm Price \$

for Access Permittees

Available from the
Division of Technical Information Extension
P. O. Box 1001
Oak Ridge, Tennessee

~~CONFIDENTIAL~~

GEMP-530

C-44a Nuclear Technology -
Materials
M-3679 (51st Edition)

UNCLASSIFIED

**SUMMARY REPORT -
HIGH TEMPERATURE MATERIALS
ENGINEERING PROPERTIES EVALUATIONS
(TASK 57017)**

J.B. Conway and W.L. McCullough

August 18, 1967

NOTICE

This report was
States, nor the
A. Makes a
racy, complete
of any informat
privately owned

B. Assume
use of any infor

As used, it
ployee or conti
such employee
disseminates, or provides access to, or
with the Commission, or his employment with such contractor.

This report was prepared as an account of work sponsored by the United States Government. Neither the United States nor the United States Atomic Energy Commission, nor any of their employees, nor any of their contractors, subcontractors, or their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness or usefulness of any information, apparatus, product or process disclosed, or represents that its use would not infringe privately owned rights.

ited
ccu-
use
inge
n the
em-
that
ares,
tract

United States Atomic Energy Commission Contract No. AT (40-1)-2847

**NUCLEAR MATERIALS and PROPULSION OPERATION
NUCLEAR TECHNOLOGY DEPARTMENT
NUCLEAR ENERGY DIVISION**

GENERAL ELECTRIC

Cincinnati, Ohio 45215

~~CONFIDENTIAL~~

~~RESTRICTED DATA~~

THIS DOCUMENT CONTAINS RESTRICTED DATA
AS DEFINED IN THE ATOMIC ENERGY ACT OF
1954, ITS TRANSFER OR THE DISCLOSURE OF
ITS CONTENTS IN ANY MANNER TO AN UN-
AUTHORIZED PERSON IS PROHIBITED.

GROUP 1

EXCLUDED FROM AUTOMATIC DOWNGRADING
AND DECLASSIFICATION.

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

UNCLASSIFIED

DISTRIBUTION OF THIS DOCUMENT IS LIMITED
To Government Agencies and Their Contractors

~~CONFIDENTIAL~~

DISTRIBUTION

EXTERNAL

AEC Headquarters

G. K. Dicker	W. L. R. Rice
D. E. Erb	F. C. Schwenk
H. G. Hembree	J. M. Simmons
	M. J. Whitman

AEC, CAO

C. L. Karl

AEC, Division of Naval Reactors

R. H. Steele

AEC, Division of Space Nuclear Systems

B. W. Colston	J. A. Powers
---------------	--------------

AEC, RDT-OSR (GE-NMPO)

J. F. Weissenberg

AEC, RDT-OSR (ORNL)

D. F. Cope

AEC, OROO

W. J. Larkin	D. S. Zachry, Jr.
--------------	-------------------

AF Weapons Laboratory

Lt. D. Brooks

Argonne National Laboratory

A. Amorosi	R. Mayfield
H. Kittel	R. Noland

Atomics International

C. E. Weber

Battelle-Northwest

F. W. Albaugh	J. J. Cadwell
---------------	---------------

BMI

S. Paprocki

General Atomic

D. Ragone

Institute for Defense Analyses

R. C. Hamilton

Jet Propulsion Laboratory

J. Davis

LASL

R. D. Baker

Lawrence Radiation Laboratory

C. Cline	A. J. Rothman
----------	---------------

L. W. Roberts B. Rubin

NASA Headquarters

J. J. Lynch

NASA, Lewis Research Center

J. W. Creagh	F. E. Rom	N. D. Sanders
T. P. Moffitt	L. Rosenblum	N. Saunders
T. A. Moss	H. Schwartz	N. R. Thielke

ORNL

W. R. Grimes P. Patriarca(2)

W. O. Harmes

Sandia Corporation (Albuquerque)

R. P. Stromberg J. Jacobs

Westinghouse, Astronuclear Lab.

D. C. Goldberg

UNCLASSIFIED

INTERNAL

D. H. Ahmann	E. S. Collins	G. Korton	F. C. Robertshaw
J. Barnard, NTD	J. F. Collins	J. E. McConnelee	E. J. Schmidt, ATS
W. G. Baxter	P. K. Conn	W. L. McCullough	J. D. Simpson
J. C. Blake	J. B. Conway	J. A. McGurty	H. R. Stephan
B. Bonini	D. H. Culver	L. S. Moody, IPO	R. E. Tallman
G. E. Booth	H. S. Edwards	J. W. Morfitt	C. O. Tarr
H. C. Brassfield	E. W. Filer	J. Moteff	P. P. Turner
R. W. Briskin	R. E. Fryxell	G. T. Muehlenkamp	F. O. Urban
C. C. Browne	P. N. Flagella	D. L. Newsom	J. E. VanHoomissen,
L. P. Bupp, NL	E. S. Funston	C. E. Niemeyer	NTPO
V. P. Calkins	A. B. Greninger, NTD	W. E. Niemuth	G. R. VanHouten
B. A. Chandler	J. O. Hibbits	G. W. Pomeroy	H. E. Wagner
K. P. Cohen, APO	C. C. Hussey	R. Reid	V. C. Wilson, R&DC
C. G. Collins	L. D. Jordan	R. B. Richards, APED	R. E. Wood
			Library (5)

~~CONFIDENTIAL~~

~~CONFIDENTIAL~~

CONTENTS

UNCLASSIFIED

	Page
INTRODUCTION	5
MECHANICAL PROPERTIES	5
Fueled Composites	5
Specimen Fabrication	5
Tensile Properties	6
Creep-Rupture Properties	8
Refractory Metal Tubing	25
Mo - 50Re	25
W - 30Re - 30Mo	27
Tantalum	27
T-111	30
PHYSICAL PROPERTIES	33
Thermal Expansion	33
W - 25Re - 30Mo	33
Unclad and Ta-Clad W-(54UO ₂ - 6ThO ₂)	33
Electrical Resistivity	34
Tantalum Tubing	35
Ta-Clad W-(54UO ₂ - 6ThO ₂)	35
SUMMARY AND CONCLUSIONS	39
Fueled Composites	39
Mechanical Properties	39
Refractory-Metal Tubing	39
Mo - 50Re	39
W - 30Re - 30Mo	39
Tantalum	39
Ta - 8W - 2Hf	39
Physical Properties	40
Thermal Expansion	40
Electrical Resistivity	40
APPENDIX	41

~~CONFIDENTIAL~~

~~CONFIDENTIAL~~

UNCLASSIFIED

4
~~CONFIDENTIAL~~

~~CONFIDENTIAL~~

SUMMARY REPORT- HIGH-TEMPERATURE MATERIALS ENGINEERING PROPERTIES EVALUATIONS

(57017)

INTRODUCTION

This summary report covers the work performed under AEC Contract No. AT(40-1)-2847 on Job 57017, "High-Temperature Materials Engineering Properties Evaluations," which terminated at the end of fiscal year 1967.

The objective of this program was to obtain specific material property data for several refractory metals and alloys and for certain refractory-metal - UO_2 composite structures with and without stabilizing additions. Such data were to be obtained over a relatively broad temperature range (room temperature to 2000°C) to furnish the information required for a detailed analysis of the performance capabilities of such materials under conditions corresponding to various potential high-temperature applications.

MECHANICAL PROPERTIES

FUELED COMPOSITES

Tensile and creep-rupture properties were determined for several fuel composites with W, W-Re, and Mo matrices. Various lots of specimens, representing different processing variables tested in helium or in $\text{He} + 5$ volume percent H_2 , showed significantly different creep-rupture properties. Details of the various test methods are given in the Appendix.

Specimen Fabrication

Agglomerated fuel, used in all the fueled composite specimens, was prepared by dry blending a 9 to 1 volume ratio of 0.8-micron particle size UO_2 and 2.0-micron particle size ThO_2 , pressing at 3515 kg/cm^2 , pulverizing in a muller, screening to 44- to 74-micron particle size, firing in helium for 2 hours at 550°C , and rescreening to 44- to 74-micron particles. Batch numbers (e.g., TF-245) were assigned for future reference.

All composite specimens were prepared by the same process except for the method of blending and the subsequent furnace cycles designed to obtain stoichiometric fuel. The basic process consisted of mechanically blending the fine refractory-metal powder with the agglomerated fuel, isostatic pressing in a rubber or plastic mold approximately 1.3 cm diameter by 13 cm long at 2812 kg/cm^2 , prefiring at 1000°C , and then sintering at 2200°C for 1 hour in dry ($\sim -55^\circ\text{C}$ dewpoint) hydrogen.

The blending techniques for lots designated 0 and 1 consisted of roll blending for 30 minutes at 78 rpm in 60 cm^3 glass jars containing three nylon balls. Starting with Lot 2, glass jars containing three metal fins were used in place of the nylon balls. This im-

~~CONFIDENTIAL~~

~~CONFIDENTIAL~~

proved blending, since fewer agglomerates of metal matrix or fuel particles were observed. Lot 2C specimens were blended in the same way as Lot 2 but were sintered for 2 hours at 2200°C instead of the 1 hour used for the other lots.

Another important difference between the lots of material involved the various post-sintering furnace cycles employed. This variety reflects a several-year span of changing technology although each cycle produced essentially stoichiometric fuel.

Lot 0 specimens were tested in the as-sintered condition and therefore contained approximately 0.3 percent uranium metal.

Lots 1 and 2 were treated for 18 hours at 1400°C in line hydrogen bubbled through water to produce a +5° to +10°C dewpoint. After machining to size these specimens were treated for 18 hours in dry hydrogen at 1200°C. The post-sinter wet-hydrogen treatment was designed to oxidize the free U present. The second treatment in dry hydrogen supposedly reduced any excess oxygen to avoid a hyperstoichiometric condition.

Further development revealed that the wet-hydrogen treatment was unnecessary and that moisture and/or oxygen present in the hydrogen was sufficient to oxidize any free metal in 18 hours at 1200°C. Lot 2A received a single 18-hour, 1200°C dry-hydrogen treatment. Lot 2B was the same as 2A except that chemistry and metallography indicated the presence of free U after the first treatment, due to an exceptionally pure and dry shipment of hydrogen gas. The 18-hour, 1200°C furnace cycle was repeated to obtain stoichiometric fuel.

Lot 2C material contained W and Re powder in the volume ratio of 0.926 W and 0.074 Re [W - 3Re - (54UO₂ - 6ThO₂); vol %]. The powders were dry impact blended for 1 hour, then dry blended in the finned jar, isostatically pressed, and sintered for 2 hours at 2200°C. After machining, the specimens were treated for 16 hours at 1200°C in purified hydrogen of -29°C dewpoint, plus 4 hours in dry purified hydrogen containing less than 5 ppm H₂O and less than 0.3 ppm total other impurities.

The compositions of the materials processed using the different procedures and the type of mechanical testing performed are summarized in Table 1.

Tensile Properties

Tensile properties of the fueled composites were determined as described in the Appendix. All elevated-temperature tests were performed in either a helium or He + 5% H₂ atmosphere.

W-(UO₂-ThO₂) - The tensile data for the W-matrix fuel composites with three different fuel loadings are presented in Table 2. Based on the data at 25°C for Lots 0 and 1 material and neglecting strain rate differences, the strength appears to increase with increasing W content. However, Lot 2A with 40 volume percent W had comparable strength to Lot 0 with 60 W. This was attributed to the effects of the different processing variables upon strength, which are discussed in the section on creep-rupture properties, where a more pronounced effect of the processing variables was observed. There was a trend toward increased strength with increased test temperature. This is not uncommon for brittle materials which show some ductility at elevated temperatures. For these materials, ductility increased from essentially no elongation at 25°C to 1.6 percent elongation at 1650°C. A typical tensile stress - strain curve for Lot 2A material tested at 1370°C is shown in Figure 1. Based on only a few points for the Lot 2A material at 1650°C, a factor of 10 increase in strain rate appeared to slightly increase the ultimate tensile strength.

Mo-(54UO₂ - 6ThO₂) - The tensile data for Lots 1 and 2 material are presented in Table 3. Although considerable spread was observed for both the ultimate strength and modulus values, the data appeared realistic for the material and there may be a correlation between fuel batch and the ultimate strength. As with the W-matrix fuel composites, there was an

~~CONFIDENTIAL~~

CONFIDENTIAL

7

TABLE 1
A SUMMARY OF MECHANICAL PROPERTIES MEASURED FOR VARIOUS COMPOSITES

Composition, vol %	Lot 0		Lot 1		Lot 2		Lot 2A		Lot 2B		Lot 2C	
	Creep- Rupture	Tensile	Creep- Rupture	Tensile	Creep- Rupture	Tensile	Creep- Rupture	Tensile	Creep- Rupture	Tensile	Creep- Rupture	Tensile
W - (36UO ₂ - 4ThO ₂)		25 °C 1100 °C										
W - (45UO ₂ - 5ThO ₂)	1370 °C 1650 °C 1930 °C	25 °C										
W - (54UO ₂ - 6ThO ₂)			1370 °C 1650 °C 1930 °C	25 °C	1650 °C	25 °C 816 °C 1093 °C 1370 °C 1650 °C	1370 °C 1650 °C 1930 °C	1370 °C 1650 °C				
Mo - (54UO ₂ - 6ThO ₂)			1370 °C 1650 °C	25 °C 816 °C 1093 °C					1650 °C			
W - 3Re - (54UO ₂ - 6ThO ₂)											1650 °C	25 °C 816 °C 1370 °C 1650 °C

UNCLASSIFIED

CONFIDENTIAL

~~CONFIDENTIAL~~

TABLE 2
TENSILE DATA FOR W-(UO₂-ThO₂) COMPOSITE MATERIALS TESTED IN HELIUM

Specimen ^a Composition	Fuel Batch No. ^b	Lot	Density, % theoretical	Temperature, °C	Strain Rate, 10 ⁻³ min ⁻¹	Ultimate Strength, kg/mm ²	Elastic Modulus, 10 ³ kg/mm ²	Elongation, ^c %
W-(36UO ₂ -4ThO ₂)	—	0	95.9	25 ^d	0.75	6.7	21.3	nil
	—	0	95.7	25 ^d	0.75	7.9	18.3	nil
	—	0	95.7	25 ^d	0.75	7.8	20.4	nil
	—	0	—	1100	0.114 ^e	15.0	17.2	0.4
	—	0	—	1100	0.114 ^e	10.4	29.3	—
	—	0	—	1100	0.114 ^e	8.2	19.4	—
	—	0	—	1100	0.114 ^e	11.8	32.3	0.2
	—	0	—	1100	0.114 ^e	7.0	13.8	0.2
W-(45UO ₂ -5ThO ₂)	—	0	94.5	25 ^d	0.75	5.6	18.2	nil
	—	0	95.7	25 ^d	0.75	4.6	19.1	nil
	—	0	95.5	25 ^d	0.75	5.2	16.3	nil
W-(54UO ₂ -6ThO ₂)	TF247	1	94.2	25 ^d	5.0	4.0	8.6	nil
	TF247	1	94.8	25 ^d	5.0	3.7	10.3	nil
	TF326	2A	94.9	25 ^d	0.75	7.5	16.1	0.1 ^f
	TF328	2A	95.0	25 ^d	0.75	8.5	15.7	0.1
	TF328	2A	95.2	25 ^d	0.75	6.3	17.8	0.1 ^f
	TF326	2A	94.7	816	5.0	10.3	14.2	0.2 ^f
	TF328	2A	94.9	816	5.0	10.4	15.7	0.4
	TF328	2A	95.3	816	5.0	10.8	—	0.3
	TF326	2A	94.0	1093	5.0	6.6	17.7	0.3 ^f
	TF328	2A	95.7	1093	5.0	11.0	—	0.5
	TF328	2A	94.8	1093	5.0	9.8	—	0.4 ^e
	TF328	2A	95.2	1093	28.0	7.9	9.6	0.4
	TF326	2A	95.0	1370	5.0	13.6	—	0.4
	TF328	2A	96.7	1370	5.0	12.5	—	0.7 ^e
	TF329	2A	95.9	1370 ^g	20.0	15.0	—	0.3
	TF329	2A	95.2	1370 ^g	5.0	14.7	—	0.2
	TF328	2A	95.5	1370 ^g	5.0	13.3	—	0.4
	TF328	2A	94.9	1370 ^g	10.0	15.9	—	0.2
	TF328	2A	94.9	1650 ^g	5.0	11.6	—	0.7
	TF328	2A	95.6	1650 ^g	5.0	11.7	—	0.7 ^f
	TF328	2A	95.2	1650 ^g	5.0	10.7	—	0.9
	TF328	2A	95.5	1650 ^g	8.0	10.0	—	0.6 ^f
	TF328	2A	95.4	1650 ^g	10.0	11.1	—	0.4
	TF328	2A	95.8	1650 ^g	50.0	13.3	—	0.6
	TF328	2A	95.6	1650	50.0	13.4	5.4	1.6

^aSpecimens were 0.32-cm in diameter.

^bFuel Batch No.: assigned to each batch of agglomerated fuel.

^cIn 2.54-cm gage length.

^dTested in air.

^eCross head speed in 10⁻³ cm/min.

^fFailed outside gage length.

^gTested in helium + 5% hydrogen.

increase in strength with increasing test temperature at least to 1370°C and a corresponding increase in ductility. At 1650°C, an appreciable amount of ductility (~6% elongation) was observed. A typical stress-strain curve at 1650°C is shown in Figure 2.

W-3Re-(54UO₂-6ThO₂) - Rhenium was added to the W matrix of Lot 2A composite material to increase the ductility of the matrix. The tensile properties of this material (designated Lot 2C) from room temperature to 1650°C are presented in Table 4. The addition of Re did not enhance the ductility of the composite material compared to the Lot 2A material (Table 2). However, it did appear to increase the tensile strength at 816°C and 1370°C.

Creep-Rupture Properties

Creep-rupture properties were measured in the temperature range of 1370° to 1930°C for Lot 0, W-(45UO₂-5ThO₂); Lots 1, 2, and 2A, W-(54UO₂-6ThO₂); Lots 1 and 2B, Mo-(54UO₂-6ThO₂); and Lot 2C, W-3Re-(54UO₂-6ThO₂).

~~CONFIDENTIAL~~

~~CONFIDENTIAL~~

9

TABLE 3

TENSILE DATA FOR LOT 1 AND LOT 2 Mo - (54UO₂ - 6ThO₂)^a MATERIAL TESTED IN HELIUM

Fuel Batch No. ^b	Specimen Density, % of theoretical	Temperature, °C	Ultimate Strength, ^c kg/mm ²	Elastic Modulus, 10 ³ kg/mm ²	Elongation, ^d %
<u>Lot 1</u>					
TF 249	92.4	25 ^e	5.0	11.4	nil
	—	816	9.4	6.9	0.4 ^f
	—	1093	10.2	—	0.3
	94.0	1093	11.6	13.8	0.2 ^f
TF 248	—	25 ^d	7.5	—	0 ^g
	94.2	25 ^d	8.3	14.2	0 ^g
	98.4	25 ^d	8.7	14.2	0 ^g
	93.8	816	10.3	—	—
	94.0	816	10.1	—	0.4 ^f
	—	816	10.5	11.6	nil
	93.2	1093	6.7 ^g	2.4	0.5 ^f
	93.2	1093	11.3	—	0.1 ^f
	95.4	1093	11.4	—	0.2 ^f
TF 247	—	1093	12.7 ^h	—	0.5 ^f
	—	1093	11.6	—	0.4
TF 250	93.9	25 ^e	7.2	—	0.1 ^f
	—	1093	12.1	—	0.3 ^f
	93.8	1093	9.0	—	0.1 ^f
TF 251	—	1093	11.1	—	0.1 ^f
<u>Lot 2</u>					
TF 281	96.3	25	10.9	—	0.2
	96.5	816	12.9	—	0.3 ^f
	96.5	1093	12.3	—	0.3 ^f
	96.5	1093	16.7	—	0.3 ^f
	96.4	1370	12.8	—	0.7
	96.5	1370	12.8	—	0.6
	96.3	1650	10.3	—	5.6
	96.4	1650	8.7	—	6.2
	96.5	1650	7.1 ^g	—	3.8
	—	—	—	—	—
	96.9	1650	8.2	—	1.8

^aSpecimens were 0.32-cm in diameter.

^bFuel Batch No.: assigned to each batch of agglomerated fuel.

^cStrain rate 0.005 min⁻¹

^dIn 2.54-cm gage length.

^eTested in air.

^fFailed outside gage length.

^gStrain rate 0.0025 min⁻¹.

^hStrain rate 0.0025 min⁻¹.

UNCLASSIFIED

~~CONFIDENTIAL~~

~~CONFIDENTIAL~~

Fig. 1 – Tensile stress – strain curve for Lot 2A W-(54UO₂ – 6ThO₂) rod tested at 1370°C in helium

UNCLASSIFIED

W-(UO₂-ThO₂) – The creep-rupture data for the W-(45UO₂ – 5ThO₂) and W-(54UO₂ – 6ThO₂) composites are presented in Tables 5 and 6, respectively. Although some scatter in the data is observed, the stress-rupture and linear creep rate curves in Figures 3 and 4, respectively, indicate a fairly consistent trend for each lot of material.

Weight loss and surface depletion measurements for the W-(54UO₂ – 6ThO₂) composition tested in helium showed no measurable fuel loss in 100 hours at 1650°C or in 3 hours at 1930°C. However, significant fuel depletion occurred in the longer tests at 1930°C reaching a maximum depletion depth of 0.35 mm after 193 hours (corresponding maximum weight loss was 1%). Based on this evaluation, such losses apparently lead to no adverse effects on the creep-rupture results for these composite materials between 1370° and 1930°C for several hundred hours in helium.

The rupture life of the Lot 2 material, tested only at 1650°C, appeared identical to Lot 1. However, the Lot 2 material was slightly less creep resistant than Lot 1 based on linear creep rate. From a strength consideration, the difference in blending between Lots 1 and 2 seemed to have no significant effect on the creep-rupture properties at 1650°C.

The Lot 2A material had greater rupture strength and was more creep resistant than the Lots 0, 1, and 2; Lot 2A had creep-rupture properties at 1930°C comparable to Lots 1 and 2 at 1650°C. The Lot 2A material, however, was tested in an environment of He + 5 volume percent H₂ rather than in the helium atmosphere used in testing Lots 0, 1, and 2. A certain amount of the observed strength difference in these materials is attributed to the different test environments. The use of different test atmosphere was prompted by the following results of cyclic creep tests of Lot 2 material at 1650°C and 0.70 kg/mm² in both helium and He + 5% H₂.

~~CONFIDENTIAL~~

~~CONFIDENTIAL~~

11

UNCLASSIFIED

Fig. 2 - Tensile stress-strain curve for Lot 2 Mo-(54UO₂-6ThO₂) rod tested at 1650°C in helium

TABLE 4

TENSILE DATA FOR W-3Re (54UO₂-6ThO₂) COMPOSITE MATERIAL (LOT 2C) TESTED IN HELIUM

Fuel Batch No. ^a	Density, % of theoretical	Temperature, °C	Ultimate Strength, ^b kg/mm ²	Elastic Modulus, 10 ³ kg/mm ²	Elongation, ^c %
TF 358	95.0	RT ^d	7.7		nil
TF 358	94.4	816	11.3	12.7	0.1
TF 358	94.3	1370	17.4	—	0.1 ^e
TF 358	93.9	1370	15.5	20.0	0.1 ^e
TF 358	95.2	1650	12.4	13.0	0.9
TF 358	94.8	1650	13.4	12.2	0.5 ^e

^aFuel Batch No.: assigned to each batch of agglomerated fuel.

^b0.005 min⁻¹ strain rate.

^cIn 2.54-cm gage length.

^dTested in air.

^eFailed outside gage length.

~~CONFIDENTIAL~~

TABLE 5
CREEP-RUPTURE RESULTS FOR LOT 0 W - (45UO₂ + 5ThO₂)^a IN HELIUM^b

Temperature, °C	Stress, kg/mm ²	Time To Indicated Strain, hr												Rupture		Linear Creep Rate, min ⁻¹
		0.1%	0.2%	0.3%	0.4%	0.5%	0.6%	0.8%	1.0%	2.0%	3.0%	4.0%	Time, hr	Elongation, %		
1370	5.62	0.3	1.8	—	—	—	—	—	—	—	—	—	2.05	0.22	9.3 x 10 ⁻⁶	
	4.22	0.5	3.4	7	10.4	—	—	—	—	—	—	—	11.2	0.44	5.1 x 10 ⁻⁶	
	2.81	2.2	7.5	14.6	17.8	19.2	—	—	—	—	—	—	27.5	1.8	2.6 x 10 ⁻⁶	
	1.97	2.8	9.5	17.8	22.2	25.5	—	—	—	—	—	—	105.9	4.6	1.6 x 10 ⁻⁶	
1650	4.22	0.08	0.16	0.22	0.30	0.35	0.40	0.44	—	—	—	—	0.48	1.5	2.0 x 10 ⁻⁴	
	2.46	0.10	0.40	0.68	0.99	1.27	1.52	—	—	—	—	—	1.75	4.0	5.5 x 10 ⁻⁵	
	1.76	0.20	0.60	1.00	1.28	1.50	1.68	2.00	2.25	3.40	—	—	3.54	—	3.9 x 10 ⁻⁵	
	1.12	0.72	1.6	2.2	2.9	3.7	4.7	6.6	8.55	17.7	23.1	27.7	31.8	5.7	1.7 x 10 ⁻⁵	
	0.70	0.26	1.75	4.00	7.00	9.2	11.4	15.2	19.0	44.0	—	—	—	—	6.2 x 10 ⁻⁶	
1930	2.25	0.01	0.04	0.08	0.11	0.15	0.18	0.25	0.33	0.63	0.86	—	1.05	4.0	4.6 x 10 ⁻⁴	
	1.69	0.03	0.10	0.18	0.25	0.33	0.40	0.54	0.70	1.37	1.86	—	2.13	4.1	2.4 x 10 ⁻⁴	
	1.12	0.061	0.13	0.23	0.33	0.41	0.50	0.69	0.85	1.67	2.40	3.05	3.55	4.6	1.8 x 10 ⁻⁴	
	0.70	0.14	0.33	0.53	0.73	0.94	1.13	1.53	1.97	3.6	5.55	7.55	13.1	7.3	8.0 x 10 ⁻⁵	
	0.49	0.31	0.74	1.18	1.68	2.10	2.55	3.50	4.5	9.5	15.0	20.8	23.7	7.9	2.7 x 10 ⁻⁵	
	0.35	0.90	2.15	3.65	5.20	6.90	8.75	12.5	16.8	39.0	61.0	79.0	123.7	7.8	7.2 x 10 ⁻⁶	

^a0.32-cm-diameter by 2.54-cm-long gage section.

^bAnnealed 15 minutes at test temperature in He before testing.

UNCLASSIFIED

CONFIDENTIAL

CONFIDENTIAL

CONFIDENTIAL

TABLE 6

CREEP-RUPTURE RESULTS FOR W - (54UO₂ - 6ThO₂)^a MATERIAL TESTED IN HELIUM

Temperature, °C	Fuel Batch No. ^b	Specimen Density, % of theoretical	Stress, kg/mm ²	Time to Give Indicated Strain, hr											Rupture			Linear Creep Rate, min ⁻¹
				0.1%	0.2%	0.3%	0.4%	0.5%	0.6%	0.8%	1.0%	2.0%	3.0%	4.0%	Time, hr	Elongation, %		
Lot 1																		
1370	TF247	92.9	1.97	4.5	9.0	13.8	18.5	23.7	28.9	41.0	54.5	—	—	—	74.3	2.5	2.5 × 10 ⁻⁶	
	TF247	93.3	2.81	1.4	11.75	—	—	—	—	—	—	—	—	—	20.2	1.3	1.4 × 10 ⁻⁶	
	TF247	93.6	4.22	0.75	2.6	4.05	5.4	—	—	—	—	—	—	—	5.4	1.0	9.5 × 10 ⁻⁶	
	TF246	93.6	5.62	0.3	1.6	2.3	3.5	4.7	5.8	7.35	8.8	—	—	—	10.1	1.5	1.4 × 10 ⁻⁵	
1650	TF247	—	0.70	1.00	2.0	3.2	4.4	5.6	7.0	9.6	12.2	26.6	40.8	54.2	96.2	8.0	1.2 × 10 ⁻⁵	
	TF246	—	1.05	1.0	2.0	2.9	3.9	4.9	5.8	7.8	9.7	19.1	26.0	33.7	38.4	5.0	1.7 × 10 ⁻⁵	
	TF247	94.1	1.76	0.21	0.4	0.6	0.8	0.98	1.38	1.56	1.94	3.85	—	—	4.6	3.0	8.6 × 10 ⁻⁵	
	TF245	91.3	1.76	0.15	0.7	1.4	2.3	3.2	4.0	5.8	7.5	15.9	22.6	26.5	30.2	5.0	1.5 × 10 ⁻⁵	
1930	TF246	94.1	2.46	0.07	0.19	0.41	0.46	0.84	1.1	1.5	1.9	—	—	—	2.9	2.0	7.5 × 10 ⁻⁵	
	TF246	92.9	0.35	0.30	1.60	3.4	5.0	6.8	8.4	12.1	17.05	42.0	67.0	91.6	192.9	15.0	6.7 × 10 ⁻⁶	
	TF247	94.3	0.49	0.20	0.62	1.2	1.61	2.2	2.65	3.75	4.8	10.5	15.1	19.7	45.1	13.0	3.7 × 10 ⁻⁵	
	TF247	95.1	0.70	0.015	0.05	0.12	0.18	0.23	0.29	0.41	0.53	1.10	1.66	2.3	3.6	11.4	3.0 × 10 ⁻⁴	
	TF247	94.3	0.84	0.04	0.07	0.14	0.20	0.25	0.3	0.40	0.49	0.9	1.28	1.61	2.0	7.8	4.5 × 10 ⁻⁵	
	TF247	92.6	1.69	0.03	0.10	0.16	0.21	0.28	0.35	0.45	0.58	1.18	1.54	1.84	2.6	9.0	2.8 × 10 ⁻⁴	
	TF246	93.1	2.25	0.03	0.05	0.08	0.12	0.15	0.18	0.28	0.37	0.8	1.08	1.27	1.4	5.0	3.8 × 10 ⁻⁴	
Lot 2																		
1650	TF281	94.2	0.56	0.25	1.74	3.9	6.2	8.5	10.6	14.8	18.5	38.5	57.8	75.0	195.8	28.0	8.0 × 10 ⁻⁶	
	TF281	95.5	0.70	0.36	1.25	2.15	3.2	4.15	5.2	7.3	9.5	20.4	44.0	53.5	173.5	25.0	1.7 × 10 ⁻⁵	
	TF281	95.0	1.05	0.2	0.46	0.75	1.03	1.3	1.6	2.13	2.67	5.4	7.8	9.9	23.2	17.8	7.8 × 10 ⁻⁵	
	TF281	95.9	1.76	0.04	0.15	0.28	0.45	0.60	0.78	1.11	1.45	3.0	4.4	5.5	12.2	13.0	1.0 × 10 ⁻⁴	
	TF281	95.1	2.46	0.01	0.05	0.10	0.18	0.25	0.35	0.48	0.6	1.18	1.68	2.1	3.6	8.8	2.3 × 10 ⁻⁴	
Lot 2A ^c																		
1370	TF328	95.1	3.52	1.7	29.0	45.7	62.5	—	—	—	—	—	—	—	78.0 ^d	0.64	1.0 × 10 ⁻⁶	
	TF328	94.9	4.22	0	3.5	11.8	19.5	27.5	35.0	49.5	61.3	109.4	—	—	140.3	3.6	2.2 × 10 ⁻⁶	
	TF328	95.2	5.62	0.2	1.6	9.1	15.7	20.0	23.5	29.7	35.4	—	—	—	51.0	2.3	2.0 × 10 ⁻⁶	
	TF328	95.7	7.03	0.10	1.1	7.1	11.3	14.0	16.0	19.5	22.9	—	—	—	23.0	1.9	3.5 × 10 ⁻⁶	
1650	TF328	95.9	0.70	1.8	20.0	49.0	87.0	122.5	153.0	206.0	252.1	—	—	—	360.0 ^d	2.75	4.3 × 10 ⁻⁷	
	TF328	94.2	0.70	1.2	18.0	44.0	78.0	110.0	143.0	200.0	—	—	—	—	203.0 ^d	—	5.3 × 10 ⁻⁷	
	TF328	95.3	1.76	0.94	5.0	9.4	14.0	18.9	23.5	32.0	35.0	72.5	97.0	117.0	170.8	11.3	4.3 × 10 ⁻⁶	
	TF328	94.2	2.46	0.17	1.0	2.8	4.8	6.8	8.8	12.6	16.2	31.1	44.0	—	45.1	5.35	1.0 × 10 ⁻⁵	
	TF328	94.6	3.51	0.13	0.75	1.4	2.1	2.8	3.4	4.8	6.0	11.9	16.0	19.4	26.4	9.53	2.8 × 10 ⁻⁵	
1930	TF328	95.2	0.70	0.21	1.2	2.4	3.4	4.6	5.7	8.0	10.5	22.0	32.0	40.0	91.2	27.4	1.5 × 10 ⁻⁵	
	TF328	95.8	1.41	0.04	0.17	0.34	0.54	0.78	1.0	1.5	2.0	4.7	7.1	—	20.8	—	6.4 × 10 ⁻⁵	
	TF328	95.9	2.11	0.02	0.08	0.16	0.24	0.32	0.40	0.57	0.73	1.6	2.5	3.2	5.4	12.8	1.9 × 10 ⁻⁴	

^a0.32-cm diameter with 2.54-cm-long gage length.^bFuel Batch No. : assigned to each batch of agglomerated fuel.^cTested in He + 5% H₂.^dTest terminated; no rupture.

UNCLASSIFIED

CONFIDENTIAL

~~CONFIDENTIAL~~

Fig. 3 — Stress-rupture data for W-(45UO₂-5ThO₂) and W-(54UO₂-6ThO₂) rod material

~~CONFIDENTIAL~~

CONFIDENTIAL

Fig. 4 - Linear creep rate data for W-(45UO₂-5ThO₂) and W-(54UO₂-6ThO₂) rod material tested in He or He + 5% H₂

UNCLASSIFIED

CONFIDENTIAL

~~CONFIDENTIAL~~

In an evaluation of the effect of temperature and load cycling on the creep resistance of Lot 2 material, a significant decrease in creep rate was observed in a He + 5% H₂ atmosphere compared to the results obtained in helium. In this testing the procedure consisted of:

1. Heating the specimen to test temperature
2. Applying the load
3. Holding at test temperature until creep-strain reached approximately 1 percent
4. Rapid cooling to room temperature
5. Removing the load
6. Reheating to test temperature
7. Reloading and holding at test conditions until an additional 1 percent creep-strain was accumulated
8. Repeating this process to rupture.

Creep strain versus time plots of the cyclic tests in both helium and He + 5% H₂ are shown in Figure 5. The curves labeled A represent the control specimens tested in helium involving no cycles; curves B and C represent the cycled specimens tested in helium and show a rapid acceleration of the creep rate indicating a considerable degradation of the creep strength; curves D and E represent the cycled specimens tested in He + 5% H₂ after the first cycle. While the creep rate of curve D is greater than that of the control specimens (curves A), neither of the specimens tested in He + 5% H₂ indicates an appreciable acceleration of the creep rate. This is shown more clearly in Figure 6 which is a plot of the ratio of the creep rate during the n-th cycle to the creep rate during the first cycle as a function of the number of cycles.

Metallographic examination of the cycled specimens showed no microcracking of W, but appreciable fracturing of the fuel particles occurred. Under polarized light the fuel in the specimens tested in helium appeared to be more hyperstoichiometric than the fuel in the specimens tested in the He + 5% H₂ atmosphere.

Fig. 5 - Cyclic creep rupture data for sintered W-(54UO₂-6ThO₂) rod (Lot 2) tested at 1650°C and 0.7 kg/mm² in various gases

~~CONFIDENTIAL~~

Fig. 6 - Ratio of creep rate versus thermal cycle number for sintered W-(54UO₂-6ThO₂) creep-rupture tested at 1650°C and 0.7 kg/mm² in various gases

To clarify the results obtained in the cyclic and constant load tests when 5 percent hydrogen was added to the helium atmosphere, Lot 2A material was tested at 1650°C and 0.7 kg/mm² to 1 percent strain in helium and in He + 5% H₂. The results for duplicate tests are shown in Figure 7 indicating that the addition of hydrogen enhances the creep properties of the material. However, this effect does not account for the total difference in creep-rupture properties between Lots 0, 1, and 2 and Lot 2A. The times (83 and 107 hr) to reach 1 percent strain in helium for Lot 2A were still about ten times greater than those noted for Lots 1 and 2 (12.2 and 9.5 hr, respectively). Metallographic examination of the test specimens showed no significant fracturing of the fuel particles in the specimens tested in He + 5% H₂, but there was considerable fracturing of the fuel particles in the specimens tested in helium, as shown in Figure 8.

Unknown differences in the fuel distribution in these cermetes can cause significant variations in strength properties. The large variations in the creep-rupture data for these lots of material, however, are postulated to be due to basic process differences. The known differences between the three lots of material are in the processing methods used to achieve stoichiometric fuel after sintering to a hypostoichiometric composition in dry hydrogen. In the wet - dry hydrogen treatment used for Lots 1 and 2, the as-sintered hypostoichiometric cermet is probably oxidized to a hyperstoichiometric composition in the wet-hydrogen treatment at 1400°C and then reduced to no lower than UO_{2.000} in the dry-hydrogen treatment at 1200°C. In the dry-hydrogen-only treatment at 1200°C, given the Lot 2A material, the hypostoichiometric composition was oxidized to probably no higher than UO_{2.000}. Whether the UO_{2.000} composition was completely achieved in either of these treatments is questionable; in fact, these treatments might have led to two different compositions. It is not possible to accurately analyze W-(UO₂-ThO₂) cermetes for small variations about the

~~CONFIDENTIAL~~

Fig. 7 - Summary of 1.0% creep tests of Lot 2A W-(54UO₂-6ThO₂) material at 1650°C and 0.70 kg/mm²

stoichiometric composition of UO₂. The differences in the creep-rupture properties observed in the helium and He + 5% H₂ atmospheres may also be related to a change in O/U ratio in the fuel of the cermet during testing. At 1650°C, the partial pressure of oxygen would be greater in helium than in He + 5% H₂; thus, the O/U ratios of the fuel in the two atmospheres would diverge with time. If the greater creep rate in helium is due to increasing oxygen content and/or a hyperstoichiometric composition, this could explain the deviation observed in the creep curves of Figure 7 after about 30 hours. According to these meager data, the changes in stoichiometry of the fuel during processing and during testing may influence creep-rupture properties.

Mo-(54UO₂ - 6ThO₂) - Creep-rupture data for Lot 1 material at 1370°C and 1650°C in helium and Lot 2B at 1650°C in He + 5% H₂ are presented in Table 7 and in Figures 9, 10, and 11. For the two lots of material and different test environments (He versus He + 5% H₂), there appears to be little difference in either creep-rupture strength or creep rates, at least at 1650°C. There was no noticeable fuel depletion in specimens tested up to 237 hours at 1650°C.

Rupture data for arc-cast Mo sheet tested in hydrogen are included in Figure 9 and illustrate the close agreement between the data for Mo and the Mo-(54UO₂ - 6ThO₂). This agreement may be fortuitous, however, since powder metallurgy refractory metals at high temperature are usually stronger than arc-cast materials.

The lack of significant difference in strength between Lots 1 and 2B, due either to process variables or to test environment (He versus He + 5% H₂) observed for the W-(54UO₂ - 6ThO₂)

~~CONFIDENTIAL~~

~~CONFIDENTIAL~~

19

Tested in He + 5% H₂ for 203 hours (Neg. 8518)

UNCLASSIFIED

Tested in helium for 117.5 hours (Neg. 8347)

Fig. 8 - Lot 2A W-(54UO₂-6ThO₂) material creep tested to 1% strain at 1650°C and 0.7 kg/mm² (250X)

~~CONFIDENTIAL~~

CONFIDENTIAL

TABLE 7
 CREEP-RUPTURE RESULTS FOR LOT 1 Mo - (54UO₂ - 6ThO₂)^a MATERIAL^b TESTED IN HELIUM AND LOT 2B Mo - (54UO₂ - 6ThO₂)^a TESTED IN He + 5% H₂

Temperature, °C	Fuel Batch No. c	Specimen Density, % of theoretical	Stress, kg/mm ²	Time to Give Indicated Strain, hr										Rupture		Linear Creep Rate, min ⁻¹	
				0.1%	0.2%	0.3%	0.4%	0.5%	0.6%	0.8%	1.0%	2.0%	3.0%	4.0%	Time, hr		Elongation, %
Lot 1																	
1370	TF248	93.5	2.81														
	TF248	93.4	2.81	0.8	4.0	8.3	12.4	17.5	24.0	46.5	73.5	190.5			15.4	0.5	2.47 x 10 ⁻⁶
	TF248	94.0	2.81	2.75	20.0	41.0	62.0	83.5	104.5	147.5					237.1		1.25 x 10 ⁻⁶
	TF248	94.2	3.52	0.22	1.42	3.5	5.2	6.9	8.55	11.9	15.28	24.2			154.9 ^d		7.8 x 10 ⁻⁷
	TF248	92.8	4.22	0.18	0.8	1.45	2.13	2.77	3.47	4.8	6.15			25.2	2.8	9.8 x 10 ⁻⁶	
	TF248	93.9	4.92	0.15	1.7	3.6	5.7	8.2	11.8	19.9	26.8			8.6	2.3	2.5 x 10 ⁻⁵	
	TF248	93.9	4.92	0.03	0.26	0.95	1.45	1.9	2.3	3.0	3.5			39.7	1.8	6.1 x 10 ⁻⁶	
	TF248	93.3	5.62	0.06	0.25	0.72	1.2	1.67	2.15	3.1	4.06	6.76		4.1	1.9	3.7 x 10 ⁻⁵	
	TF251	92.3	2.11	0.03	0.12	0.37	0.63	0.9	1.16	1.66	2.07	3.63	4.2		6.8	3.2	3.4 x 10 ⁻⁵
1650	TF248	93.2	2.11	0.02	0.14	0.4	0.67	0.94	1.2	1.74	2.27	4.54	5.97		4.5	4.0	6.33 x 10 ⁻⁵
	TF248	92.8	1.41	0.03	0.32	0.85	1.35	1.9	2.45	3.53	4.6			6.9	4.0	6.25 x 10 ⁻⁵	
	TF248	92.6	1.05	0.6	1.6	2.6	3.3	4.0	4.8	6.3	7.9			8.6	2.0	3.12 x 10 ⁻⁵	
	TF248	93.8	0.70	0.25	2.0	4.25	7.0	10.1	13.4	20.25	27.9	15.5	23.1	30.0	62.3	11	2.18 x 10 ⁻⁵
	TF248											57.0	74.9	90.8	159.4	12	5.6 x 10 ⁻⁶
Lot 2B																	
1650	TF337	97.3	0.281	20.5	47.0	76.2	117.5	167.8	225.4								
1650	TF337	97.2	0.70	2.7	7.6	12.0	16.0	19.8	23.5	29.8	35.6	66.4	93.8	118.5	264.8	14.6	7.0 x 10 ⁻⁶
1650	TF337	96.9	1.41	0.12	0.46	1.4	2.2	3.2	4.2	5.9	7.7	14.0	19.0	23.3	27.8	9.0	2.1 x 10 ⁻⁵
1650	TF337	96.9	2.11	0.07	0.22	0.38	0.55	0.75	0.94	1.3	1.6	3.0	4.1	4.9	5.2	6.6	9.2 x 10 ⁻⁵

^aComposition is in volume percent.

^b0.32-cm diameter with 2.54-cm-long gage length.

^cFuel Batch No.: assigned to each batch of agglomerated fuel.

^dSample did not rupture; furnace failed.

^eDid not rupture; heating element failure, possible over-temperature.

UNCLASSIFIED

CONFIDENTIAL

Fig. 9 - Stress-rupture results for Lots 1 and 2B Mo-(54UO₂-6ThO₂) rod material tested in helium or He + 5% H₂

UNCLASSIFIED

Fig. 10 - Linear creep rate results for Lots 1 and 2B Mo-(54UO₂-6ThO₂) rod material tested in helium or He + 5% H₂

~~CONFIDENTIAL~~

Fig. 11 - Creep-rupture results for Lots 1 and 2B Mo-(54UO₂-6ThO₂) rod material

composite, is not understood. This may be related to the fact that Mo will dissolve free U in the hypostoichiometric fuel formed during sintering whereas W shows no solubility for U.

W-3Re-(54UO₂-6ThO₂) - Creep-rupture data at 1650°C in He + 5% H₂ at three stress levels are presented in Table 8. Time-to-rupture and linear creep rate data are compared to data for the W-(54UO₂-6ThO₂), Lot 2A, composite material in Figures 12, 13, and 14. The addition of Re to the W matrix did not apparently influence the creep-rupture properties at 1650°C.

~~CONFIDENTIAL~~

CONFIDENTIAL

TABLE 8

CREEP-RUPTURE DATA FOR LOT 2C W - 3Re - (54UO₂ - 6ThO₂) ROD MATERIAL TESTED IN HELIUM + 5% HYDROGEN

Temperature, °C	Fuel Batch No. ^a	Specimen Density, % of theoretical	Stress, kg/mm ²	Time to Give Indicated Strain, hr												Rupture		Linear Creep Rate, min ⁻¹
																Time, Elongation, ^b		
				0.1%	0.2%	0.3%	0.4%	0.5%	0.6%	0.8%	1.0%	2.0%	3.0%	4.0%	hr	%		
1650	TF358	94.3	1.05	0.6	5.0	9.0	16.9	23.0	26.9	39.7	54.0	109.5	158.0	194.0	391.7	23	2.9 x 10 ⁻⁶	
1650	TF358	94.3	1.76	0.9	2.6	5.0	7.5	10.25	13.1	18.85	24.5	48.0	66.6	82.5	141.7	18.5	6.0 x 10 ⁻⁶	
1650	TF358	95.2	2.81	0.16	0.57	0.91	1.25	1.59	1.94	2.69	3.7	8.9	14.4	18.5	37.5	15.3	3.1 x 10 ⁻⁵	

^aFuel Batch No. : assigned to each batch of agglomerated fuel.^b0.32-cm diameter with 2.54-cm-long gage length.

UNCLASSIFIED

CONFIDENTIAL

~~CONFIDENTIAL~~

Fig. 12 - Stress-rupture data for Lot 2C W-3Re-(54UO₂-6ThO₂) rod material tested at 1650°C in He + 5% H₂

UNCLASSIFIED

Fig. 13 - Linear creep rate data for Lot 2C W-3Re-(54UO₂-6ThO₂) rod material tested at 1650°C in He + 5% H₂

~~CONFIDENTIAL~~

Fig. 14 - Creep-rupture results for lot 2C W-3Re-(54UO₂-6ThO₂) rod material tested at 1650°C in He + 5% H₂

REFRACTORY-METAL TUBING

Refractory-metal tubing with small bore and thin wall is required for coolant passages in refractory-metal fuel elements. Tensile properties from room temperature to 1750°C were measured for Mo-50Re (wt %), W-30Re-30Mo (at. %), Ta, and T-111 (Ta-8W-2Hf, wt %). In addition, creep-rupture properties were measured at 1600° to 1650°C for Mo-50Re and T-111. The tubing tested contained no defect or wall variation greater than 10 percent of the wall thickness. Specimen description and test method are described in the Appendix to this report.

Mo-50Re

The Mo-50Re (wt %) tubing from a commercial source was fabricated by consolidation of powders using powder metallurgy techniques, extruded, wrought, and drawn to tubing of 0.42-cm OD by 0.038-cm wall thickness. This material was received and tested in the recrystallized condition.

Tensile Properties - Tensile data were obtained at room temperature, 800°, 1200°, and 1600°C in helium. The results are presented in Table 9 and shown graphically in Figure 15. These tubes showed some variation in wall thickness (less than 10%) which probably accounts for the numerous fractures outside the gage length; for these specimens, the reported percent elongation values are probably low.

Creep-Rupture Properties - Creep-rupture tests conducted at 1600°C in helium at four stress levels are presented in Table 10 and Figures 16, 17, and 18. In Figures 16 and 17, the stress-rupture and linear creep rate data are compared to those reported for powder metallurgy Mo-50Re sheet in hydrogen.¹ The creep-strain data are plotted in Figure 18. From the limited amount of data, the tubing tested in helium appeared to have a lower rupture life and to be less creep-resistant than the sheet material tested in hydrogen. This difference could be attributed to differences in form (tube versus sheet), variations in wall thickness (less than 10%), or to different sources of materials observed to affect the creep-rupture properties of powder metallurgy W, W-25Re, and Mo sheet.²

¹P. N. Flagella and C. O. Tarr, "Creep-Rupture Properties of Rhenium and Some Alloys of Rhenium at Elevated Temperatures," GE-NMPO, GE-TM 65-9-12, October 3, 1965, p. 11.

²"Fifth Annual Report - High-Temperature Materials Program, Part B," GE-NMPO, GEMP-400B, February 28, 1966, pp. 29-33.

~~CONFIDENTIAL~~

TABLE 9

TENSILE TEST RESULTS FOR Mo - 50Re AND T-111 (Ta - 8W - 2Hf) TUBING^a

Material	Temperature, °C	Ultimate Tensile Strength, kg/mm ²	0.2% Yield Strength, ^b kg/mm ²	Elongation, ^c %	Modulus of Elasticity, 10 ³ kg/mm ²
Mo - 50Re	25 ^d	96.3	—	8.5 ^e	—
	25 ^d	97.0	84.3	10.0 ^e	36.3
	25 ^d	100.4	89.8	8.5	38.9
	800	57.4	—	17.0 ^e	—
	1200	19.3	—	15.0 ^e	—
	1600	7.2	—	25.0 ^e	—
T-111	25 ^d	69.0	—	15.0 ^e	—
	25 ^d	67.1	55.8	21.0 ^e	19.8
	25 ^d	67.8	55.8	27.5 ^e	22.8
	300	46.3	34.0	6.0 ^e	—
	600	40.3	—	3.5 ^e	—
	800	38.0	30.5	—	13.6
	800	37.1	—	3.0	12.2
	1200	36.2	34.3	3.5 ^e	9.6 ^f
	1600	20.8	18.9	15.0	7.6

^aNominal dimensions: 0.42-cm OD x 0.34-cm ID.^b0.005 min⁻¹ strain rate.^c2.54-cm gage length.^dTested in air.^eBroke outside original gage length.^fRadial cracks.

UNCLASSIFIED

Fig. 15 - Effect of temperature on the tensile strength and ductility of Mo - 50Re tubing tested in helium

~~CONFIDENTIAL~~

TABLE 10
CREEP-RUPTURE DATA FOR Mo - 50Re TUBING^a TESTED AT 1600°C IN HELIUM

Stress, kg/mm ²	Time to Give Indicated Strain, hr									Rupture Time, hr	Linear Creep Rate, min ⁻¹
	0.1%	0.3%	0.6%	1.0%	1.5%	2.0%	3.0%	5.0%	10.0%		
1.05	0.15	0.70	1.73	9.3	14.6	20.4	32.0	56.0	125.0	413.5	1.2×10^{-5}
1.05	0.017	0.25	1.00	4.05	8.5	13.0	22.0	36.7	66.0	130.7	1.8×10^{-5}
1.41	—	0.23	0.86	1.6	2.55	3.45	5.0	7.7	13.0	26.2	9.9×10^{-5}
2.11	—	—	0.10	0.28	0.54	0.79	1.23	1.95	3.34	7.0	3.3×10^{-4}
2.81	0.01	0.016	0.06	0.12	0.18	0.24	0.35	0.54	0.95	2.8	1.6×10^{-3}

^a0.42-cm OD x 0.038-cm-thick wall.

Fig. 16 - Stress-rupture data for Mo - 50Re tubing tested at 1600°C in helium

UNCLASSIFIED

W - 30Re - 30Mo

The W - 30Re - 30Mo (at. %) tubing from a commercial source was fabricated using powder metallurgy techniques, extruded, wrought, and drawn to tubing of 0.17-cm OD by 0.025-cm wall thickness. This tubing was tested in helium in the recrystallized condition.

Tensile Properties - The tensile data obtained at room temperature, 1200°, and 1750°C are presented in Table 11 and Figure 19.

Tantalum

The Ta tubing from a commercial source was fabricated using powder metallurgy techniques, extruded, wrought, and drawn to 0.17 cm OD by 0.025-cm wall thickness. It was tested in the stress-relieved condition.

Tensile Properties - This tubing was tested at room temperature, 1200°, and 1750°C. The data are presented in Table 11 and Figure 19. The ultimate strength and modulus-of-rupture data agree with those published in the literature. However, the elongation values at all temperatures were lower than the value reported for stress-relieved Ta sheet.³

³"The Engineering Properties of Tantalum and Tantalum Alloys," DMIC Report 189, September 13, 1963.

~~CONFIDENTIAL~~

Fig. 17 - Linear creep rate data for Mo - 50Re tubing tested at 1600°C in helium

UNCLASSIFIED

Fig. 18 - Creep strain data for Mo - 50Re tubing tested at 1600°C in helium

~~CONFIDENTIAL~~

~~CONFIDENTIAL~~

29

TABLE 11
TENSILE TEST RESULTS FOR W-30Re-30Mo AND TANTALUM TUBING

Material ^a	Test Temperature, °C	Atmosphere	Testing Speed		Ultimate Tensile Strength, kg/mm ²	Elongation, % in 2.54-cm gage length	Modulus Of Elasticity, kg/mm ²
			cm/cm-min ^b	cm/min ^c			
W-30Re-30Mo (at. %) tubing	RT	Air	0.00075		86	0.3	32.8 x 10 ³
	RT	Air	0.00075		94.9	4.0	31.3 x 10 ³
	1200	He		0.114	40	5.4	-
	1750	He		0.229	8.37	-	-
	1750	He		0.229	8.76	6.3	-
Ta tubing	RT	Air	0.00075		38.12	0.2	-
	1200	He		0.229	8.30	10.0	-
	1200	He		0.229	8.65	7.6	-
	1750	He		0.114	2.60	10.0	-

^aNominal dimensions of 0.17 cm OD by 0.025 cm wall thickness.

^bStrain rate, obtained from strain pacer.

^cFree crosshead speed.

Fig. 19 - Tensile data for tantalum and W-30Re-30Mo (at. %) tubing (0.17 cm OD by 0.025 cm wall thickness)

~~CONFIDENTIAL~~

CONFIDENTIAL**T-111 (Ta - 8W - 2Hf)**

The T-111 tubing, purchased commercially, was fabricated as arc-cast material, extruded, wrought, and drawn to tubing, 0.42 cm OD by 0.038 cm wall thickness. It was tested in the stress-relieved (1 hour at 1230 °C) condition.

Tensile Properties – Tensile tests were performed at room temperature, 300°, 600°, 800°, 1200°, and 1600 °C in helium; data are presented in Table 9 and Figure 20. As in the tests of Mo - 50Re, most of the specimens broke outside the gage length; thus, the reported percent elongation values are probably low.

Creep-Rupture Properties – Two tests of T-111 tubing were completed at 1650 °C in helium; both samples, however, were severely contaminated with oxygen and nitrogen as shown in Table 12 and Figure 21. The source of contamination was evidently the additional outgassing of furnace components heated to 1650 °C, which was above the normal outgassing conditions of 1000 °C at 10^{-4} Torr used before the test.

Fig. 20 – Effect of temperature on the tensile strength and ductility of T-111 alloy tubing tested in helium

CONFIDENTIAL

CONFIDENTIAL

31

TABLE 12

RESULTS OF CREEP-RUPTURE TESTING ARC-CAST T-111 TUBING^a
AT 1650°C IN HELIUM

Stress, kg/mm ²	Rupture Time, hr	Linear Creep Rate, min ⁻¹	Hardness, DPH			Chemical Analysis, ppm		
			OD	Center	ID	N ₂	O ₂	H ₂
	as-received		297	274	274	18	61	5
7.03	3.2	7.5×10^{-4}	322	297	322	-	-	-
5.62	36.2	7.9×10^{-5}	464	572	464	750	1629	2

^a0.42-cm OD x 0.038-cm-thick wall.

Outside
diameter

Inside
diameter

a. As-received (Neg. 7342, 250X)

Outside
diameter

Inside
diameter

b. Reduced section after creep-rupture testing at 1650°C and 5.62 kg/mm² for 36.2 hours in helium showing contaminated structure (Neg. 7343, 250X)

Fig. 21 - T-111 alloy tubing

CONFIDENTIAL

~~CONFIDENTIAL~~

UNCLASSIFIED

~~CONFIDENTIAL~~

~~CONFIDENTIAL~~

UNCLASSIFIED

PHYSICAL PROPERTIES

Measurements were made of the linear thermal expansion characteristics of the W - 25Re - 30Mo (at. %) alloy to 2500 °C, and of unclad and Ta-clad W-(54UO₂ - 6ThO₂) to 2000 °C. Electrical resistances of Ta-tubing and Ta-clad W-(54UO₂ - 6ThO₂) were also measured.

THERMAL EXPANSION

Linear thermal expansion measurements were made using the method of Conway⁴ which involved the sighting of paired filar micrometer microscopes on fiducial marks near the end of a rod or specially shaped sheet specimen.

W - 25Re - 30Mo

Thermal expansion to 2500 °C in helium was obtained for both a sheet sample of 0.027-cm-thick sheet and a 0.58-cm-diameter rod. Both samples were fabricated at GE-NMPO by powder metallurgy techniques. Results for both specimens are shown in Figure 22 which includes the computed thermal expansion curve based on a simple volume fraction summation of individual components of the alloy. With the exception of two points for the sheet specimen, both the sheet and rod agree very well with each other and with the calculated curve.

Unclad and Ta-Clad W-(54UO₂ - 6ThO₂)

Thermal expansion measurements of unclad and Ta-clad W-(54UO₂ - 6ThO₂) were made up to 2000 °C in helium. One unclad specimen was formed from material cut transverse to the die-pressing direction; another was cut parallel to the die-pressing direction. These two specimens were originally made up in segments, encapsulated in Ta, and autoclaved; the cladding was then removed by centerless grinding. One Ta-clad (0.025-cm-thick) specimen was isostatically pressed. Other slight differences in the fabrication procedures were:

	<u>Clad</u>	<u>Unclad</u>
Agglomerated fuel particle size, microns	37 to 44	44 to 63
Hydrogen treatment	Wet and dry	Dry
Autoclave time at 1650 °C and 700 kg/cm ² , hours	1	3

Thermal expansion data are presented in Figure 23. Both unclad specimens yielded identical data, indicating that the material was isotropic at least with respect to thermal expansion. The expansion data for the Ta-clad specimen are identical to Ta⁵ up to 1400 °C. Above

⁴J. B. Conway, "Properties of Some Refractory Metals, III Thermal Expansion Characteristics," GE-NMPO, GEMP-375, June 29, 1965, pp. 11-16.

⁵J. B. Conway, R. M. Fincel, Jr., and A. C. Losekamp, "Effects of Contamination on the Thermal Expansion of Tantalum," *Transactions of the Metallurgical Society, AIME*, Vol. 233, 1965, p. 841.

~~CONFIDENTIAL~~

~~CONFIDENTIAL~~

Fig. 22 - Thermal expansion of powder metallurgy W-25Re-30Mo (at. %) tested in helium

this temperature, the clad-composite data are higher than those for pure Ta; at 2000°C they are 10 percent higher. This behavior is similar to that reported⁵ for contaminated Ta in which distortion of the expansion curve to higher values was noted above 1200°C when impurity absorption occurred. This may have occurred in the Ta-clad composite specimen as a permanent increase in length (0.05 mm) was observed after the first heating.

Least squares computer analyses led to the following polynomial expressions for the curves in Figure 23:

Unclad W-(54UO₂ - 6ThO₂)

$$\frac{L_T - L_{25^\circ\text{C}}}{L_{25^\circ\text{C}}} \times 100 = 2.08 \times 10^{-2} + 3.28 \times 10^{-4}T + 2.18 \times 10^{-7}T^2$$

applicable in the temperature range 25° to 1800°C where T is in °C.

Ta-Clad W-(54UO₂ - 6ThO₂)

$$\frac{L_T - L_{25^\circ\text{C}}}{L_{25^\circ\text{C}}} \times 100 = 7.35 \times 10^{-3} + 4.17 \times 10^{-4}T + 2.19 \times 10^{-7}T^2$$

from 25° to 2000°C where T is in °C.

ELECTRICAL RESISTIVITY

Tantalum-clad W-(54UO₂ - 6ThO₂) specimens were electrically heated to evaluate the thermal stability and heat transfer characteristics of the composite. To determine the

~~CONFIDENTIAL~~

Fig. 23 - Linear thermal expansion data for W-(54UO₂-6ThO₂) measured in helium

electrical power distribution, resistance measurements were made of the Ta tubing and Ta-clad W-(54UO₂-6ThO₂).

Tantalum Tubing

The room-temperature electrical resistance of Ta tubing both as-received and after a 1-hour anneal at 1650°C in vacuum was measured. The resistances for the two conditions were the same as shown in Table 13.

Ta-Clad W-(54UO₂-6ThO₂)

The combined electrical resistance as a function of length was determined for a Ta-clad W-(54UO₂-6ThO₂) rod sample (Fig. 24) containing 13 core cylinders with lapped interfaces (Fig. 25) to determine whether core interfaces affect the total electrical resistance. This assembly was autoclaved at 1650°C and 7.03 kg/mm² for 1 hour in helium to bond the core interfaces and the cladding to the core. The room-temperature resistance data are given in Table 14. No significant effect of the interfaces on the resistance was observed.

To determine the thermal stability of the assembly and the amount of power necessary to simulate nuclear heating, the specimen was electrically heated three times to 1600°C in a static helium atmosphere at approximately 150°C/min with no adverse effects and no apparent hot spots on the surface of the rod. The physical changes and power requirements are shown in Tables 15 and 16, respectively. Very small diametral changes were observed. The 0.03-gram weight increase was probably due to contamination, since bottled helium was used with no additional purification and no "getter" was used to protect the specimen.

~~CONFIDENTIAL~~

TABLE 13
ELECTRICAL RESISTANCE OF TANTALUM
TUBING^a AT ROOM TEMPERATURE

Test Length, cm	Resistance, ohms/cm	
	As-Received	After 1-Hour Anneal At 1650°C
2.54	9.06×10^{-5}	—
5.08	9.049×10^{-5}	9.060×10^{-5}
7.62	9.044×10^{-5}	9.062×10^{-5}
10.16	9.044×10^{-5}	—
12.70	9.029×10^{-5}	—
15.24	9.045×10^{-5}	—

^aNominal 1.350 cm OD by 0.038 cm wall thickness.

Fig. 24 – Tantalum-clad W-UO₂, sample ER-1, used to determine the combined electrical resistance (Neg. P65-10-15)

Fig. 25 – Cross section sketch of Ta-clad W-(54UO₂ + 6ThO₂) sample ER-1 used to determine the combined electrical resistance

~~CONFIDENTIAL~~

~~CONFIDENTIAL~~

37

TABLE 14

ELECTRICAL RESISTANCE OF W- UO_2 ROD CLAD
WITH TANTALUM TUBING^a AT
ROOM TEMPERATURE

Position ^b	Test Length, cm	Number Of Interfaces	Resistance, ohms/cm
1 - 2	2.543	4	1.850×10^{-5}
2 - 3	2.526	4	1.870×10^{-5}
3 - 4	2.540	4	1.880×10^{-5}
1 - 4	7.609	12	1.867×10^{-5}
4 - 5	6.990	0	1.908×10^{-5}
1 - 5	14.599	12	1.887×10^{-5}

^aTa cladding, nominal 0.038 cm wall thickness.

^bSee Figure 25.

TABLE 15

RESULTS OF RESISTANCE HEATING A Ta-CLAD W- UO_2 ROD
IN HELIUM

	Diameter at Specimen Position, ^a cm					Weight, g
	1	2	3	4	5	
Pre-test	1.338	1.337	1.337	1.339	1.340	352.19
Post-test	1.340	1.340	1.340	1.340	1.340	352.22

^aSee Figure 25.

UNCLASSIFIED

TABLE 16

POWER REQUIRED TO HEAT A
Ta-CLAD W- UO_2 ROD

Mean Surface Temperature, °C	Power Required, kw
1100	1.5
1425	2.7
1600	3.6

^aSee Figure 25.

~~CONFIDENTIAL~~

~~CONFIDENTIAL~~

UNCLASSIFIED

~~CONFIDENTIAL~~

~~CONFIDENTIAL~~

UNCLASSIFIED

SUMMARY AND CONCLUSIONS

FUELED COMPOSITES

Mechanical Properties

W-(UO₂-ThO₂) – Tensile and creep-rupture properties of W-(UO₂-ThO₂) for three fuel loadings show:

1. Tensile strength increased with increased W content and with increased test temperature to 1650°C. Correspondingly, there was a slight increase in ductility from essentially zero percent elongation at room temperature to 1.6 percent at 1650°C.
2. Creep-rupture strengths in the 1370° to 1930°C temperature range showed a wide variation in rupture life for W-(54UO₂ – 6ThO₂) rods when processed by different methods to achieve a stoichiometric fuel after sintering to a hypostoichiometric composition. Similarly, the test environment (He versus He + 5% H₂) had a significant effect on stress-rupture strength. This may be due to the stoichiometric changes in the fuel during processing and testing in different environments.

Mo-(54UO₂ – 6ThO₂) – An increase in tensile strength and ductility was exhibited by Mo-(54UO₂ – 6ThO₂) with increase in test temperature at least to 1370°C. At 1650°C this material had a 6.1 percent elongation. For two lots of material and different test environments (He versus He + 5% H₂), there was little difference in creep-rupture strength or creep rates at 1650°C.

W – 3Re – (54UO₂ – 6ThO₂) – This composite material, in which Re was added to the W matrix to enhance ductility, had essentially the same tensile and creep-rupture properties as W-(54UO₂ – 6ThO₂).

REFRACTORY-METAL TUBING

Mo – 50Re

Tensile tests to 1600°C and creep-rupture tests at 1600°C showed that Mo – 50Re thin-wall tubing had lower ductility, lower stress-rupture life, and lower creep resistance than powder metallurgy sheet material.

W – 30Re – 30Mo

Tensile properties of W – 30Re – 30Mo were determined at room temperature, 1200°, and 1750°C.

Tantalum

The ultimate strength and modulus-of-rupture data for Ta thin-wall tubing up to 1750°C compared favorably with sheet data in the literature, but the elongation values were considerably lower.

Ta – 8W – 2Hf

Short-time tensile tests of Ta – 8W – 2Hf to 1600°C yielded satisfactory data, but in the longer time creep-rupture tests at 1650°C, the specimens became contaminated with oxygen and nitrogen, negating test results.

~~CONFIDENTIAL~~

~~CONFIDENTIAL~~

PHYSICAL PROPERTIES

Thermal Expansion

Thermal expansion data were presented for W - 25Re - 30Mo to 2500°C and for unclad and Ta-clad W-(54UO₂ - 6ThO₂) to 2000°C. For the W - 25Re - 30Mo alloy, the data corresponded to the computed curve based on a simple volume fraction summation of individual component data. The expansion of unclad W-(54UO₂ - 6ThO₂) was isotropic, at least for specimens cut transverse and parallel to die pressing direction. With Ta-cladding, the expansion was identical to pure Ta up to 1400°C. Above 1400°C, the Ta-clad composite expansion became greater than for Ta; it was 10 percent higher at 2000°C.

Electrical Resistivity

The room-temperature electrical resistivity of Ta tubing and autoclaved Ta-clad multiple-core cylinders of W-(54UO₂ - 6ThO₂) showed no effect of core interfaces. The Ta-clad specimen was electrically heated to 1650°C in helium with no adverse effects and no apparent hot spots.

~~UNCLASSIFIED~~~~CONFIDENTIAL~~

~~CONFIDENTIAL~~

APPENDIX

TENSILE AND CREEP-RUPTURE TESTING

TEST METHODS

Specimen Types

Tensile and creep-rupture testing was performed with rod and tube specimens. The rod specimens used for testing the fueled composite materials were machined from sintered powder metallurgy rods to the configuration shown in Figure A1, with a gage section 0.32 cm in diameter by 3.18 cm in length. The tubing specimens were 30-cm long in order to have the grip fixtures outside the high-temperature zone (Figure A2). Also shown are the targets for measuring strain (also used for the rod specimens) and the black-body tube for measuring temperature. The grips and targets are shown in more detail in Figure A3.

Test Facilities

The test facilities for creep-rupture testing were the same as described elsewhere⁶ for testing sheet specimens. Essential details are shown in Figures A4 and A5. For tensile testing, the constant-load application chamber was eliminated and an O-ring-sealed load cell arrangement was inserted to permit the use of a tensile machine for load application.

Strain Measurement

Strain in the rod and tube specimens was measured optically. For the slower strain rates of the creep-rupture tests, paired, filar micrometer telescopes, focused on the targets attached at either end of the specimen gage length, were adjusted manually to follow the elongation under load. For the more rapid strain rates employed in tensile testing, an electro-optical extensometer (Optron)* was used. This instrument optically follows the motion of a fiducial mark with a resolution of 10^{-4} cm, and an accuracy of 1 percent of the total range, at strain rates up to 1500 sec^{-1} .

Using the Optron, a technique was developed for strain pacing tensile tests at elevated temperatures. The specimen strain versus load relationship was automatically plotted while the specimen strain rate was simultaneously compared to a reference strain rate. Manual control of the tensile machine was maintained to match the pre-selected strain rate. Strain pacing was accomplished with the Optron system by retransmitting a proportioned strain signal on a load-strain plot. The specimen's retransmitted strain was compared to a pre-selected strain rate on a second recorder. The strain rate was controlled by varying the specimen loading rate. Corresponding to the desired strain rate, parallel lines on the pacing recorder were used as a guide in adjusting the loading rate to obtain the desired constant strain rate as shown in Figure A6. The corresponding load-strain curve is shown in Figure A7.

⁶W. L. McCullough and P. N. Flagella, "Experimental Techniques Employed in Stress-Rupture and Creep Measurements to 3000°C," GE-NMPO, GE-TM 65-5-10, April 29, 1965.

*Registered trade name of Optron Corporation, Santa Barbara, California.

~~CONFIDENTIAL~~

~~CONFIDENTIAL~~

UNCLASSIFIED

Fig. A-1 – Configuration of rod specimens for testing power-metallurgy composite materials

Fig. A-2 – Refractory-metal tube specimen for tensile testing to 2000°C showing strain and temperature measuring targets (Neg. P65-10-10A)

~~CONFIDENTIAL~~

Fig. A-3 - Welded grip-end and targets employed in testing tubing

Fig. A-4 - 2800°C stress-rupture and creep test rig (Neg. P65-12-28A)

~~CONFIDENTIAL~~

Fig. A-5—Artist's sketch of 2800°C stress-rupture and creep test furnace (AS-170)

Temperature Measurement

To measure temperature of the rod-type specimen, a calibrated optical pyrometer was sighted in a black-body hole in a small tube suspended beside the rod specimen. For the tube-type specimens, an optical pyrometer was sighted on the black-body target (see Figure A3) attached to the specimen.

Start-Up Procedure

The start-up procedure for both rod- and tube-type specimens was the same. The specimens with targets attached were inserted in the test chamber and heated to 1000°C in vacuum until 10^{-4} Torr was obtained. Helium (99.9995 percent purity) or He + 5% H₂ was admitted and the desired test temperature was achieved. It was maintained for 0.25 to 1 hour to attain thermal equilibrium before the test.

~~CONFIDENTIAL~~

Fig. A-6 – Optron strain pacing for T-111 tubing tested at 800°C in helium

Fig. A-7 – Load-strain curve for T-111 tubing tested at 800°C in helium at 0.005 min⁻¹ strain rate

~~CONFIDENTIAL~~

NUCLEAR TECHNOLOGY DEPARTMENT

NUCLEAR ENERGY DIVISION

GENERAL ELECTRIC

~~CONFIDENTIAL~~