UNCLASSIFIED

MANHATTAN PROJECT SERIES

Wo-25261

CONTRIBUTION OF THE RADIATION LABORATORY OF UNIVERSITY OF CALIFORNIA

Paper No. 16

THE SUBLIMATION OF URANIUM TETRACHLORIDE

By

MANFRED E. MUELLER

LEGAL NOTICE

This report was prepared as an account of Government sponsored work. Neither the United States, nor the Commission, nor any person acting on behalf of the Commission:

A. Makes any warranty or representation, express or implied, with respect to the accuracy, completeness, or usefulness of the information contained in this report, or that the use of any information, apparatus, method, or process disclosed in this report may not infringe privately owned rights; or

B. Assumes any liabilities with respect to the use of, or for damages resulting from the use of any information, apparatus, method, or process disclosed in this report.

As used in the above, "person acting on behalf of the Commission" includes any employee or contractor of the Commission to the extent that such employee or contractor prepares, handles or distributes, or provides access to, any information pursuant to his employment or contract with the Commission.

Photostat Price \$ 16.80Microfilm Price \$ 5.70

Available from the
Office of Technical Services
Department of Commerce
Washington 25, D. C.

UNCLASSIFIED

216 001

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency Thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

DISCLAIMER

Portions of this document may be illegible in electronic image products. Images are produced from the best available original document.

CLASSIFICATION CANCELLED

DATE APR 8 1957

For The Atomic Energy Commission

T. R. Canale

Chief, Declassification Branch

~~IDENTIAL~~

ABSTRACT

This paper contains a description of experimental studies of the behavior of granular UCl_4 during sublimation under a variety of geometric and thermal conditions. On the whole, it may be said that the solid has a sublimation behavior such as might have been expected, and the results should be typical for well-behaved solids subliming in about the same temperature-pressure range. The field of research has, however, received practically no attention in the past.

It is shown that aggregates of granular UCl_4 sublime primarily from the top layer, even when impure, and that the rate of sublimation depends very much on surface conditions and impurities and is proportional to the vapor pressure of the solid. Particle size is found to be an unimportant variable, except as it affects the impurities and thermal conduction. The rate history of various aggregates and the effect of various geometries is described and is shown to involve the entry of some of the variables in unpredictable ways.

Granular UCl_4 containing about 3% UOCl_2 possesses sublimation rates varying from 0.01 to 0.25 that calculated from the vapor pressure equation. A maximum ratio of 0.9 was found for one case in which the molecular wind was sufficient to eject the impurity from the surface, suggesting that the probable f value for pure UCl_4 is unity.

Experimental results for temperature gradients through the aggregates and the temperature drop at the surface brought about by sublimation are described and are correlated with a theory of sublimation in which it is assumed that the latent heat of sublimation is supplied by

216 002

~~IDENTIAL~~

216-2

~~CONFIDENTIAL~~

radiant energy.

The use and effect of applied radiant energy was studied, with results for both sublimation rates and temperatures, and a good correspondence was obtained between the two types of results.

All the experimental work was performed on solids similar to those in actual use, and therefore the results bear directly on certain practical problems in the supply and control of UCl_4 gas.

~~CONFIDENTIAL~~

216-3

OUTLINE

I. INTRODUCTION

1. Reasons for the Experimental Studies.

II. THEORETICAL AND EXPERIMENTAL BACKGROUND

2. The Rate of Sublimation. Observations on Granular Solids.
3. Summary of the Experimental Variables.

III. CHARACTERISTICS OF THE UCl_4 USED. IMPURITIES.

4. Properties and Characteristics of the UCl_4 Used. Impurities.

IV. THE METHOD

5. The Method.
6. Validity of the Experimental Results.
7. Dependence on Thickness of Samples.

V. STUDIES RELATING TO THE CONTROL OF THE SUBLIMATION

8. Preliminary Studies.
9. Control by Orifices.

VI. STUDIES MADE WITH THE CONTROL HELD EXTERNALLY

10. Transport through Orifices.
11. Transport through Tubes.
12. Dependence of the Transport on the Length to Radius Ratio of Tubes.

VII. STUDIES MADE WITH THE CONTROL HELD BY THE SURFACE OF THE SOLID
AND IN WHICH THE TEMPERATURE IS HELD CONSTANT

13. Introduction

Part. A. TRANSPORTS ARE MEASURED.

14. Dependence on Impurities.
15. Dependence on Particle Size.
16. Dependence on the Experimental Temperature.
17. Experimental Results obtained on the Variation of the Transport with Time by the Weight Loss Method.
18. Studies made with a Vacuum Balance on the Variation of the Transport with Time as a function of several Geometric Factors.

Part. B. TEMPERATURE MEASURED.

19. Methods and Apparatus in the Measurement of Temperatures.
20. Experimental Results.
21. The Maximum Temperature Drop brought about by Sublimation.

216-4

111
~~CONFIDENTIAL~~

DECLASSIFIED

OUTLINE (Con't)

VIII. STUDIES MADE WITH THE CONTROL HELD BY THE SURFACE OF THE SOLID AND IN WHICH THE EXPERIMENTAL TEMPERATURE WAS AB-
RUPTLY ALTERED.

- 22. Description of the Method and the Experimental Schedule.
- 23. Experimental Results on Temperatures.
- 24. Conductivity of the Granular Aggregates.
- 25. Experimental Results on Transports and on the Correspondence of the Transports with Temperatures.

IX. SOME PRACTICAL CONSEQUENCES OF THE WORK.

- 26. Practical Consequences.

REFERENCES

1. (a) M. Knudsen, Ann. Physik, 28, 75, (1909), 29, 179, (1909), 47, 697, (1915).
 (b) I. Langmuir, Physical Review, 2, 329, (1913)
 (c) T. Alty and F. Nicoll, Can. J. Res. 4, 547, (1931): T. Alty, Phil. Mag. 15, 82, (1933): T. Alty, PRS (London) A131, 554, (1931): T. Alty and C.A. Mackay, PRS (London) A149, 104, (1935)
 (d) T. Alty, PRS (London), A161, 68, (1937)
 (e) F. Metzger and F. Miescher, Nature 142, 572 (1938)
 (f) K. Neumann and V. Costeanu, Z. Phys. Chem. A185, 65-80, (1939)
 (g) J.P. Blewett, H.A. Liebhaufsky, and E.F. Hennelly, J. Chem. Phys. 7, 478, (1939)
 (h) D.B. Langmuir and L. Malter, Phys. Rev. 55, 748, (1939)
 (i) W. Prueger, Z. Physik, 115, 202, (1940)
 (j) H.L. Johnson and A.L. Marshall, J.A.C.S. 62, 1382, (1940)
 (k) H. Spingler, Z. Phys. Chem. B52, 90, (1942)
 (m) R. Schuman and A.B. Garrett, J.A.C.S. 66, 442 (1944)
2. M.E. Mueller. Manhattan Project Series. Contribution of the Radiation Laboratory of the University of California. Paper No. 12. "The Vapor Pressure of Uranium Halides". July 1946
3. (a) P.D. Crout, J. Math. and Phys. M.I.T. 15, 1, (1936): H.A. Giddings and P.D. Crout, ibid, 15, 125, (1936)
 (b) G.E. MacWood. Manhattan Project Series. Contribution of the Radiation Laboratory of the University of California. Paper No. 11. "Theory of Sublimation of Solids".
4. (a) M.E. Mueller and M.L. Armstrong: RL 4.6.192, Aug. 24, 1943. "Preliminary Results on the Effect of Water Vapor Contamination; RL 4.6.213, Oct. 8, 1943 "Preliminary Study of the Change in Sublimation Rate with Particle Size", RL 4.6.214 Oct. 9, 1943, "The Effect of Moisture on the Sublimation Rate of Material of Different Particle Size"; RL 4.6.215, Oct. 12, 1943 "The Effect of Depth on the Sublimation Rate"; RL 4.6.228, Nov. 12, 1943 "The Relationship between Rate and Time."
 (b) M.E. Mueller, RL 4.6.257, May 5, 1944 "Sublimation of UCl_4 . Summary of Experimental Variables which enter into Sublimation".
 (c) M.E. Mueller and Iva Streeter, RL 4.6.267, "Rate of Sublimation. History of UCl_4 Charges of Varying Geometry".
 (d) M.E. Mueller, P.H. Davidson, and Iva Streeter, RL 4.6.910, Feb. 12, 1945 "Temperature Effects of Sublimation"
 (e) M.E. Mueller, RL 4.6.939, Oct. 22, 1945. "The Effect of Radiant Energy on Small Scale Aggregates of Granular UCl_4 . The Rate of Sublimation and Temperature Response of the Aggregates."
5. (a) S.H. Babcock, Jr. RL 4.6.12, Dec. 31, 1942. "The Absorption of Moisture by UCl_4 ".
 (b) P.H. Davidson and I. Streeter, RL 4.6.920, June 5, 1945. "The Equilibrium Vapor Pressure of UCl_4 above $UOCl_2$ ".
 (c) R. Krohn and A. Stein, Unpublished work, Berkeley, March, 1945.

DECLASSIFIED

216-6

REFERENCES (Con't)

- (d) M.E. Mueller, RL 4.6.191, Aug. 19, 1943. "The Wetting of UCl_4 by Water Vapor".
- (e) M.E. Mueller, RL 4.6.250, "Wet Methods for the Preparation of UCl_4 . The Properties of $UOCl_2$ ".

6. Miscellaneous References.

- (a) P.H. Davidson and I. Streeter, RL 4.6.289, Sept. 5, 1944. "The Corrosion Resistance of Nickel Alloys to UCl_4 Vapor".
- (b) E.A. Gulbransen, Trans. Electrochem. Soc. 87, 11 pp preprint, (1945) "Oxidation and Rate of Evaporation of Magnesium".
- (c) W.G. Kannalink and L.H. Martin, PRS (London) A141, 144, (1933) "The Conduction of Heat in Powders".
- (d) W.H. Smith Jr. and M.E. Mueller, RL 4.6.911, March 19, 1945 "Determination of Non-Volatile Matter in UCl_4 ".
- (e) W.H. Smith Jr. RL 4.6.919, "The Corrosion of Iron and Copper by UCl_4 Gas".

INTRODUCTION

1. Reasons for the Experimental Studies.

Before the experimental studies on the sublimation of granular UCl_4 were undertaken, the substance had become well established as the source material in the Calutron method of isotope separation, and it was generally assumed that the sublimed UCl_4 available at the time was sufficiently pure to behave as a pure solid, producing gas at a rate calculable from the vapor pressure equation.

As the Calutron units developed, it became necessary to provide variable control of the gas supply. Mechanical valves, consisting of simple butterfly valves or of rotating plates, were first introduced, and these were made with large clearances to prevent "freezing". These valves were unsatisfactory, since control of the gas was difficult to establish for even short periods of time, and the valves usually had little effect in their intended range of operation. This focussed attention on the UCl_4 , since it was evident that the solid was not subliming at a rate approaching that calculated from the vapor pressure equation. It was suggested that the hygroscopic character of UCl_4 was primarily responsible for this behavior of the solid.

Quantitative studies of the behavior of aggregates of the granular solid with added water vapor contamination were therefore made. It seemed also that interesting information could be acquired from further experimental work, and therefore studies of the characteristics of the solid during sublimation were continued through a period of ten months. In the conduct of the experimental studies, it was the primary intention to perform them in such ways as to apply the information directly to Calutron units,

216-8

DECLASSIFIED

and so the studies at first had little correspondence with simple theories concerning the sublimation of pure solids. As the work progressed, however, sufficient information having theoretical implications was gathered to make this worthwhile in itself.

It is the purpose of this paper to give a connected account of the practical and theoretical results obtained from 110 experiments performed on various problems relating to the sublimation of UCl_4 , and to integrate this information sufficiently to give a coherent description of the behavior of the substance.

A total of 460 samples were studied.

216-9

DECLASSIFIED

II.

THEORETICAL AND EXPERIMENTAL BACKGROUND.

2. The Rate of Sublimation. Observations on Granular Solids.

Sublimation is a transport phenomenon, and the two chief quantities which describe it are the net number of molecules which depart from the surfaces or pass through a hole per unit area and the effective area over which the process occurs.

Knudsen (Ref. 1a), Langmuir (Ref. 1b) and others have shown that the transport may be expressed by the equation

$$G = \sqrt{\rho_1} \frac{P_1 - P_2}{\sum W} \quad (1)$$

where G is the transport in $\text{gm./cm.}^2/\text{sec.}$, ρ_1 is the density of the gas at a pressure of 1 dyne/ cm.^2 , P_1 and P_2 are the pressures in dynes/ cm.^2 which describe the pressure difference at the surface or at an aperture in a container, and $\sum W$ represents the total resistance of the system through which the flow is occurring, in cm.^{-2} . The resistance of an orifice and of a subliming surface may be described by the equation

$$W_1 = (2\pi)^{1/2}/A \quad (2)$$

where A is the area of the orifice or surface in cm.^2 . In the consideration of the transport from the surface it is necessary to include a coefficient, f , which represents the mass-accomodation coefficient and which may also be made to include the surface resistance. With this coefficient and the usual value for $\rho_1 = \frac{M}{R_c T}$, the transport from a surface becomes:

216-10

DECLASSIFIED

$$G = fAtP \sqrt{\frac{M}{2\pi R_c T}}$$

where t is the time in seconds, P is the pressure difference at the surface or the initial pressure itself for flow into a vacuum, M is the molecular weight, R_c is the gas constant, and T is the surface temperature in $^{\circ}\text{K}$. For UCl_4 , this equation becomes

$$G_{\text{gm./cm.}^2/\text{hr}} = 4094 f T^{-1/2} P_{\text{mm.Hg}} \quad (4)$$

The vapor pressure equation for solid UCl_4 (Ref. 2) is

$$\log_{10} P_{\text{mm.Hg}} = -10644/T + 13.604 \quad (5)$$

Values for both P and G (with $f = 1$) are given in Table 1.

Equation (3) is the fundamental equation which has been used in the scientific literature for the description of evaporation rates, and considerable attention has been placed on the description of f . For those experimental studies in which the surface temperature may be stated with certainty, the value of either f or P may be calculated from the experimental values for G , and if the vapor pressure is known, then f may be evaluated directly. The substances for which the value of f has been determined are included in the following summary.

DECLASSIFIED

216-11

Substance	f	Method	Reference
-----------	---	--------	-----------

Substances whose f value is nominally equal to 1

Copper	1	Coincidence with effusion	1j
Nickel	1	" "	1j
Barium oxide	1	" "	1g
Mercury	1 (0.958)	Measured T and G, know P	1a
Cadmium	1		?
CCl ₄ , C ₆ H ₆	1		1i
I ₂ , Naphthalene	1	" " "	1d
HgCl ₂	0.76 ± .1	" " "	1e
HgBr ₂	0.64 ± .1	" " "	1e
HgI ₂	0.53 ± .1	" " "	1e

Polar substances whose f value is nominally less than 1

KReO ₄	0.8	Measure T and G, know P	1f
Benzoic Acid	less than 0.29	" " "	1d
Synthetic Camphor	0.17	" " "	1d
Water (liq.)	app. 0.036	" " "	1c
C ₂ H ₅ OH	very small		1c
NH ₄ Cl	small		1k

Substances for which f has been assumed to be equal to 1:

Tungsten (Ref. 1b), Tantalum (Ref. 1h), Beryllium (Ref. 1m).

Alty (Ref. 1d) has pointed out that the f value for non-polar molecules may be expected to be equal to 1, and for polar molecules may be considerably less. The results on mercury halides were taken by Metzger and Miescher as supporting Alty's conclusion that $f = 1$ for polar molecules. The molecules of UCl₄ are only very slightly polar, if at all, and it may be assumed that the f value for pure UCl₄ solid is equal to 1 also.

In the experimental work on granular UCl₄ it was soon realized that one of the difficulties in the path of interpreting the measurements was the inability to define the surface temperature. Almost all of the work

216-12
DECLASSIFIED

in the summary of f values just given was based on assemblies of fairly high thermal conductivity, so that the surface temperature was essentially that of the reservoir to which the material was attached, and Alty and others also measured the surface temperature directly, when possible. The thermal conductivity of granular aggregates (see Section 24) remains quite small until moderate vapor pressures are attained. Then evaporation and condensation within the aggregate accounts for a good deal of the internal conductivity. Other than that the heat must arrive at the surface by radiation from the surroundings. The lowering of the surface temperature below that of the underlying solid was observed in the first experiments employing material finer than 10 mesh by the formation of small inverted cones of interlaced crystals just below the surface, but no estimates of surface temperature were made at the time.

It is a logical consequence of the above observations to consider that if the heat arrives at the surface of the solid primarily by radiation from the surroundings that the simple theory represented by equation (3) must be altered to fit granular solids. This was done by the author in November, 1943 by calculating the temperature drop required to allow heat to reach the surface by radiation as fast as heat was required by latent heat of sublimation. A simple combination of equations (4) and (5) with the Stefan-Boltzmann Radiation Law is all that is required. The latent heat of sublimation of UCl_4 was taken as 48700 cal. per mole. The values arrived at, revised to fit the present vapor pressure equation (5), and introducing various values of f , are given in Table 2. The emissivity of the surfaces is taken as 1. The equation which represents this simple theory on granular UCl_4 is

216-13

DECLASSIFIED

$$T_1^4 - T_2^4 = 4.086 \cdot 10^{16} (f T_2^{-1/2} P_{\text{mm}})$$

where T_1 is the temperature of the external radiating surface and T_2 is the temperature of the surface of UCl_4 .

MacWood (Ref. 3b) has developed a theory of sublimation in which he has followed the basic assumptions of Crout (Ref. 3a). He included the condition that the heat was transferred to the surfaces by radiation alone, and applied the calculations to granular UCl_4 . The theory and results are given in another collected paper of this series. Since the heat of sublimation used was an early value of 40700 calories per mole, the temperature drop values are not used directly in this paper.

3. Summary of the Experimental Variables. Definitions.

It is of some interest to arrange the experimental variables in proper order of importance, separating or combining them as the analysis requires and thus to arrive at a guide to the whole study of sublimation. This has been done in the summary which follows. In this summary the parenthesized numbers refer to the sections in this paper in which the experimental results are described.

216-14

DECLASSIFIED

SUMMARY OF EXPERIMENTAL CONDITIONS PERTAINING TO A STUDY OF SUBLIMATION

3

EXPERIMENTAL CONDITIONS VALID

Thermal environment well defined.
Pressure environment well defined.
Temperature measurements valid.
Transport measurements valid.
Sufficient solid present (7)

I.

NATURE OF PROCESS NOT
KNOWN OR CONTROL OF THE
PROCESS IS DIVIDED

- A. The process as a whole is studied.
- B. Factors relating to constant are studied
 - 1. Use of surface coverings (8)
 - 2. Orifice, valve or tube control (9)
 - 3. Thermal control (25)

II.

CONTROL IS DEFINED
AT THE SURFACE OF
THE SOLID

- A. The surface is uncontaminated; the solid is pure
- B. The surface is contaminated; the solid is impure

III.

CONTROL IS DETERMINED
BY EXTERNAL FACTORS

- A. Transports are Measured
 - 1. Geometry remains constant
 - a. Thin orifices (10)
Area and temperature varied.
 - b. Long tubes (11)
Length, diameter and temperature varied.
 - c. Short Tubes or Thick Orifices (12)
Ratio of L/R varied.

1. Thermal Environment is Constant during an Experiment.

- a. Transports are measured
 - 1. Surface conditions essentially constant.
Surface impurity varied (14)
Particle size varied (15)
Temperature varied (16)
 - 2. Surface and Mass conditions change with time
Geometric factors varied (17,18)
Impurity varied
Particle size varied
Temperature varied
- b. Temperatures are measured
 - 1. Surface conditions essentially constant
Measured as a function of the amount of impurity particle size, position (20)
 - 2. Surface and Mass conditions change with time (20)

2. Thermal Environment is Varied during an Experiment

- a. Transports are measured (25)
 - 1. Surface Conditions essentially constant
Materials and temperature varied (25)
 - 2. Surface and mass conditions change with time
- b. Temperatures are measured
 - 1. Thermal response (23)
measured as a function of material, position, and temperature
 - 2. Steady state temperatures measured as a function of material, position, and temperature (23)
 - 3. Energy delivered is varied (23)
 - 4. Dependence of all observations on changes within the solid
- c. Correspondence of temperature and transport observations (25)

216-15

The most important definition to give is that of the surface area. This is taken as the area of a plane lying within the exposed surface of the solid, and not as the actual area of the exposed particles. If one is dealing with absolutely pure material then surface irregularities do not enter since the area which counts is the projected surface determined by the direction in which the molecules must move to escape. If the surface of the solid is contaminated so that only small areas are active or if the surface is covered with a porous impurity, then the surface is best defined as above, placing any departure of the surface area from the assumed area on the f value used in equation (3).

216-16

DECLASSIFIED

III.

CHARACTERISTICS OF THE UCl_4 USED. IMPURITIES.4. Properties and characteristics of the UCl_4 used. Impurities.

→ The solid UCl_4 which was used in these studies was the same as that which was used in actual service in Calutron units. The solid was prepared by the chlorination of UO_2 by means of CCl_4 at 450°C to 500°C at Berkeley, or by the Harshaw Chemical Co. using the Berkeley method, or as prepared subsequently by the Tennessee Eastman Corporation. Some of the Harshaw material was used in these studies without sublimation. All other material was sublimed. Sublimation was performed in 30 Kg. vacuum stills at about 600°C . Large batches of the selected materials were set aside, properly screened and analyzed, and then used in small quantities.

The Harshaw UCl_4 had a UCl_4 content of 97% or better. Sublimation served the purpose of freeing the solid of volatile materials, such as C_2Cl_6 , COCl_2 , and a fairly large part of the FeCl_3 . UOCl_2 was removed to some extent, by the formation of UO_2 in the residue, but not as well as might have been expected, since this material just traveled with the UCl_4 "wind" during sublimation. The sublimed material used in these studies contained 0.2% Fe, 0.06% Cr, 0.03% Ni, $0.05 \pm 0.01\%$ HCl, and from 0.3 to 8% UOCl_2 .

UCl_4 is very hygroscopic (Ref. 5a), and the chief product of reaction with water is UOCl_2 or $\text{UOCl}_2 \cdot \text{H}_2\text{O}$ (Ref. 5e). Upon being heated in a vacuum the $\text{UOCl}_2 \cdot \text{H}_2\text{O}$ becomes UOCl_2 if heated slowly, and UO_2 if heated rapidly. UOCl_2 acts as a non-volatile material on the surface of UCl_4 granules and apparently offers fairly high resistance to flow. In the presence of UCl_4

216-17

DECLASSIFIED

vapor, UOCl_2 does not decompose (Ref. 5b), and any UO_2 which is present is converted into UOCl_2 . In its reaction with water, UCl_4 retains most of the HCl which is formed and gives this up on being heated.

The packing density of granular UCl_4 is 1.8 to 2.5 gm./cm.³, which amounts to 38% to 50% of the space occupied by the solid. The aggregates is therefore quite open in its structure. The packing density of UOCl_2 is rather small, ranging from 0.5 gm./cm.³ to 1.1 gm./cm.³. The material is filamentous in structure and does not pack well, nor does it fall off readily.

UCl_4 gas molecules are monomers (Ref. 2), and the molecular weight may be taken as 379.9.

IV. THE METHOD

5. The Method.

The principal method employed in studying the variables which entered into sublimation was the direct measurement of the weight loss of a sample before and after a cycle of operations. The apparatus, the vacuum system, the dry box, and experimental techniques have been described in a companion paper (Ref. 2., Sections 5, 20, and 30, Figures 5-9, 12), but the furnace portion of the apparatus is shown here in Figure 1. The experimental schedule, arrangement of the apparatus, important facts concerning the geometries, and the conduct of the experiments are stated in Table 3. It is not necessary to go into greater detail until the experimental results are presented.

6. Validity of the Results.

In general it may be said that measurements are valid provided the conditions under which results were obtained are known, the various experimental quantities were measured with sufficient accuracy, and the

216-18

DECLASSIFIED

variables which enter can be discussed in clear cut terms.

Vacuum.

The vacuum system was satisfactory in all experiments. The system has been described elsewhere (Ref. 2, Figure 6). It was connected to the various 3" furnace tubes shown in the figures by means of 1" i.d. Pyrex line, through a 15mm. orifice vacuum stopcock. Pressures maintained at the condensing region were usually estimated to be lower than 1×10^{-4} mm. Hg. Adequate traps and gauges were used, and it was a simple matter to collect and determine the HCl condensed in the traps.

Resistance to Flow.

Within the furnace the experimental arrangement was frequently not as good for removal of the UCl_4 vapor as could have been desired. This was due to the desire to study quite a few samples at once in the horizontal apparatus and to the study of fairly large samples in the vacuum balance and temperature studies. Some of the results suffer somewhat in their significance but are still of sufficient value to relate. Adequate records were kept of the geometries employed and it is possible to supply fair estimates of the external resistances through which the vapor had to flow to reach the condensing zone. The use of the radiation baffle in the path of the gas may be criticized for its obstruction to vapor flow ($W = 0.47 \text{ cm.}^{-2}$) but it was necessary to use it.

It is desirable at this point to include the various equations which may be used to determine the resistance to the flow of the gas which is offered by the various geometries employed. The resistance offered by a thin-edged orifice and by an uncontaminated surface with $f = 1$

216-19

DECLASSIFIED

was given as equation (2). The resistance of a long tube is given by the equation

$$W_3 = \frac{3}{8} \sqrt{\frac{\pi}{2}} \int_0^L \frac{O}{A^2} \cdot dL \quad (7)$$

where O is the perimeter, A is the cross-sectional area of the tube, and L is the length. For a cylindrical tube this becomes

$$W_4 = \frac{3}{8} \sqrt{\frac{2}{\pi}} \frac{L}{R^3} \quad (8)$$

Most of the geometries employed in this work, however, employed very short tubes. It is shown in Section 12 that the Clausing short-tube formula is satisfactory for UCl_4 gas, and the resistance for short tubes should therefore be calculated by the equation

$$W_5 = \frac{20 + 19 \frac{L}{R} + 3 \frac{L^2}{R^2}}{20 + 8 \frac{L}{R}} \sqrt{\frac{2}{\pi}} \cdot \frac{1}{R^2} \quad (9)$$

A graphical evaluation of equation (7) has been applied to the unit aperture appearing in a set of hexagonal close-packed spheres, and this has been found to be equivalent to a resistance 13.5 times as great as the resistance of the area to which it applies. Each aperture applies to an area of the solid slightly larger than half the area of a great circle. The resistance ratio is equal to 21 if the equivalent tube for the odd-shaped aperture is calculated by equation (9) instead of (7).

The resistance equations hold only for molecular flow conditions, but probably may be used at somewhat higher pressures.

216-20

DECLASSIFIED

The resistance for each typical geometry was calculated, and it is possible to select experiments from among those described which were performed with such geometries as allow a proper calculation of f .

Temperatures. Considerable care was lavished on rendering temperature measurements valid, both as to defining the thermal environment of a sample and as to the reliability of the thermocouples used. The thermocouples were all suitably standardized and compared with each other. Those used directly in the solid UCl_4 were shown to give correct measurements, even with the silver solder at the junction undergoing corrosion.

Weight Loss. Weight loss of the samples was usually interpreted with ease. However, there was some uncertainty of the origin of the HCl in experiments conducted with well baked-out charges. Davidson finally showed that the HCl originated in the condensing zone of the glass tube, where water is apparently not baked out before the UCl_4 is condensed.

Constancy of the Surfaces. Most of the early measurements were made under conditions in which the rate of sublimation was considered steady, when this was not actually the case. A single weight loss measurement per experiment allows one to determine only an average rate. The instantaneous rates must have been quite different at times, resembling those given by the light dot-dash lines on curve II in Figure 9. However, this difficulty concerning rate measurement is largely avoided by the technique of using multiple samples and blanks.

Amount of Material Present. It may be noted in subsequent sections that it is rarely necessary to discard an experimental result on account of in-

216-21
DECLASSIFIED

sufficient material in the sample, even for rather thin and small samples. This was a somewhat unexpected consequence of the experimental work which is described in the next section.

7. Dependence on Thickness of Samples.

In discussions which were held at the time the experimental work was started it was assumed that the various assemblages of granular solids which were in use either in charge bottles or in these experimental studies gave amounts of gas which were dependent on the thickness of the samples, such that one might expect much more gas from a mass three inches thick than from one which was only one inch thick. This was soon put to experimental test, and it was learned that aggregates, of loosely packed, UCl_4 provide, most of the gas from the top layer of particles and rather little from underlying layers, depending somewhat, however, on the particle size. This does not mean, however, that the gas is not moving within the solid mass.

Experimental results at $410^\circ C$ and $450^\circ C$ were obtained in experiment 16, 17, 27, and 28 with samples ranging in thickness from 2mm. to 24mm. and ranging in particle size from 4-6 mesh to 32-60 mesh. The samples were arranged in the apparatus (Figure 1) in a random fashion, and the results are shown in Figure 2. In the uppermost curve (Exp. 16, 6-10 mesh, $450^\circ C$) the 4mm. point may be discarded, since the sample would have been more than exhausted to maintain the rate of sublimation which the other samples experienced. The results shown in Figure 2 were combined with careful observation of the samples to estimate the minimum thickness required for nearly maximum rate. The region where sublimation had occurred was indicated by the yellow-

216-22

DECLASSIFIED

green UOCl_2 residues and the thickness and nature of the sintered cone or "pancake" which represented the region cooled by sublimation. The curves in Figure 2 were drawn with these observations partly in mind, and the conclusions are shown in Figure 3.

It is a clear consequence of this work that the solids containing up to 3% UOCl_2 provide most of the gas from the top layer of particles. A corollary conclusion would then be, that as the top layer is exhausted and the second and subsequent layers take over, the impurities left on the upper surface will have a much larger effect than would have been the case had a larger mass of solid participated directly in the sublimation.

These experiments were conducted under conditions where the gas coming from the twelve open samples (26 cm.² area) had to pass through the 7 cm.² cross section above the heavy block. Certainly had the samples been extremely pure this would have resulted in an important objection to the conclusions. It is felt, however, that the conclusions are valid, since the rate observations were independent of position in the heavy block and the size and shape of the region cooled by sublimation indicated that most of each of the thicker samples was not taking part in the process at all. It appears that the resistance of the impurities at the surface of the samples was sufficiently large to have rendered the effect of the 7 cm.² cross-section tube above the samples of little consequence.

It is clear therefore that in the experiments which will be described in subsequent sections there was sufficient solid present to give results which may be interpreted as being independent of the thickness of the aggregate, with the exception of those experiments in which thermal conduct-

216-23

DECLASSIFIED

ivity through the mass of solid became an important factor.

216-24

DECLASSIFIED

V.

STUDIES RELATING TO THE CONTROL
OF THE SUBLIMATION8. Preliminary Studies.

Prior to the time at which direct studies were made on obtaining control over the sublimation of solid UCl_4 , it had been shown that the particle size of the material, the non-volatile content, and the added surface impurities brought about by water vapor contamination affected the transport, and it was felt that the addition of surface coverings would lead to removal of the differences, and at the same time reduce the transport. It was hoped that it would be possible to recommend to the designers of Calutron units that a surface covering of glass chips placed on top of the solids in charge bottles would enable one to treat most materials in an identical way. This view turned out to have been naive. The elimination of differences between materials by the addition of glass bead or glass chips covers was partially successful, but not sufficiently so, due to the fact that the layers of glass particles did not offer a sufficiently high resistance. It was shown by measurement of the glass particles that the volume occupied by them ranged from 58% to 63%, and thus they allowed an average open cross-section of 40%. If one assumes that the apertures in the piles of chips or beads represent short tubes, it can be shown from molecular flow equations that the total resistance offered per layer of particles should be independent of the size of the particles of glass, and that the total resistance of the pile of particles is dependent only on the number of layers. It should therefore be possible to express all results in terms of the dependence of the observed transport on the ratio of the thickness of the glass pile to

216-25

DECLASSIFIED

the average diameter of the glass chips or beads. All the values obtained for glass beads and chips by direct comparison of the transports with those obtained with uncovered samples, and with the exception of those samples having too fine UCl_4 particles (offering too high a surface resistance) are shown in Figure 4. It is fairly clear from this figure that the results show dependency only on the number of "layers" of the glass beads or chips. Direct dependency would be indicated by a line (such as the dashed one in the figure) sloped at a 45° angle. However, this would ignore the existence a considerable resistance at the surface of the solid. By trial and error it was found possible to represent all the results obtained with glass beads and chips by a series resistance argument (the solid line in the figure) in which the average surface resistance of the UCl_4 was taken as equal to the resistance of 1.8 layers of glass beads or chips. It was stated in section 6 that the resistance of the aperture in an assemblage of glass beads is equal to from 13 to 21 times that given by equation (2), and it may be concluded that the maximum resistance offered to the flow of UCl_4 at the surface of the solid was therefore 36 times that which would have been offered by a pure solid. This calculated resistance is, however, too high, since it assumes perfect packing of the spheres or chips, with no larger apertures at the wall of the container. Since larger apertures do exist it may be assumed that the nominal surface resistance was between 10 and 20 times that offered by a pure solid.

Additional results were obtained for the effect of a screen and a perforated brass disc. 8-10 mesh UCl_4 was studied uncovered, covered with a single thickness of 44% open area stainless steel screen (0.022" holes,

216-26

DECLASSIFIED

16 mesh, 2 samples), and covered with a perforated brass disc with 29.5% open area (0.027" holes and 0.020" thick, 1 sample). The measured transports in gm./hr./cm.² of surface of the solid were 0.274 for the uncovered samples, 0.234 and 0.230 for the screen-covered samples, and 0.185 for the brass-disc-covered sample.

9. Control by Orifices.

The study of the control over sublimation was next extended to the use of orifices, which offered definable resistances. The first study was made with a set of orifices drilled in caps which were 1/8" thick. These varied in diameter from 1/32" to 1/2". It was soon found that these orifices were to be defined as short tubes, and the results obtained are given in section 12. Subsequent work was done with stainless steel and nickel caps in which the orifices had sharp edges. The side facing the solid was left flat, and the other side was cut out to leave a cone-shaped depression and a thin-edged hole. Corresponding orifices in Pyrex vessels could not be made thin enough for the smaller holes.

Preliminary results at 430°C indicated fairly rapid acquisition of control at orifice areas (A_3) approximately 1/25th those of the surface area (A_2) of the solid. Results were subsequently obtained in the temperature range from 357°C to 490°C, in a series of studies in which the study of control was combined with a careful study of the vapor pressure of UCl_4 . The numerical results have been given elsewhere (Ref. 2, Table 6), and they are shown graphically in Figure 5. In addition to the results obtained with small sample bottles, results are also shown for Exp. 38-44 for sample

316-27

DECLASSIFIED

bottles in which the surface area of the solid was 17 cm.² and 46 cm.², instead of 2.43 cm.²

In interpreting the figure it may be noted that horizontal lines across the figure indicate control by the orifice resistance, while lines at a 45° angle (the light dot-dash lines) indicate control by the resistance existing at the surface of the solid.

216-28

DECLASSIFIED

VI.

STUDIES MADE WITH THE CONTROL HELD EXTERNALLY

10. Transport through Orifices.

The transport of UCl_4 gas through orifices has been made the subject of considerable experimental investigation for the purpose of obtaining the vapor pressure of the substance by the effusion method and for extending information on the flow through orifices up to pressures where the effusion equation is ordinarily not valid. This work has been described and critically analyzed elsewhere in detail (See Ref. 2, Sections 4-11, 29-33). Measurements were made on Harshaw 4-8 mesh material, on samples of sublimed material, both having non-volatile UOCl_2 content of about 3%, and on resublimed material of much less non-volatile content. Most of the measurements on these substances have been given in Figure 5. Additional work was also done on samples of UCl_4 which had been melted and ground, and these were found to give the same vapor pressure as the other material.

The pressure range was such as to permit the conclusion that the effusion equation held for UCl_4 gas throughout the transition region from molecular flow to hydrodynamic flow and from large values of the ratios of the mean free path to the diameter of the orifice to a value of 0.025, corresponding to a pressure of 1 mm. Hg.

The vapor pressure equation from effusion measurements alone is very near to that given by equation (5).

11. Transport through Tubes.

The flow of UCl_4 gas through tubes has been studied by Davidson and Streeter in the pressure range from 0.042 to 0.673 mm. Hg. The tube resistances ranged from 9.7 to 102 cm.^{-2} as based on equation (8). The

216-29

DECLASSIFIED

surface areas of the UCl_4 samples were 4 cm.^2 for the work with tube A, and 50 cm.^2 for each of the other seven tubes. According to equation (2), the resistances for pure UCl_4 with these two areas are 0.6 cm.^{-2} and 0.05 cm.^{-2} . The maximum ratio of the resistance of the tube to that of the solid was 170 for tube A and 190 for the other tubes. This ratio was sufficiently large for the tube to retain control over the somewhat impure UCl_4 which was used. The results show no consistent deviations such as would be ascribed to too small tube resistances. The experiments gave results in which the viscous flow term ranged from 8% to 87% of the total flow.

The results have been carefully analyzed elsewhere (Ref. 2, Sections 12-15, 26, 34-36) and yielded a confirmation of the vapor pressure equation obtained by the effusion method. It was also possible to derive values for certain physical quantities. The molecular diameter of the UCl_4 gas molecule was shown to be approximately $5.6 \times 10^{-8} \text{ cm.}$, the viscosity 288 micropoises at 500° C , and the mean free path $0.0098 (T_o/P_{\text{dynes}})_K \text{ cm.}$

12. Dependence of the Transport on the Length to Radius Ratio of Tubes.

Experimental transports obtained in Experiments 35, 36, 37, 42 and in the tube flow studies have been gathered together to provide a rough confirmation of the Clausing short tube formula. If the molecular flow equation for the transport through tubes is applied to length to radius (L/R) ratios which become small, so that the tube approaches an orifice, the flow calculated from the tube equation is far too large. This is shown by the dashed line in Figure 6. The orifice flow would be 8/3 as large calculated by the tube equation as by the orifice equation. An equation is therefore needed which gives a smooth transition from the tube flow equation to the orifice flow equation, and which is correct at both extremities.

DECLASSIFIED

216-30

The Clausing short-tube formula represents such an equation and appears to be the best one which is available. The equation may be expressed as a correction factor to be applied to the orifice flow equation (equation (3), $f=1$). This correction factor is

$$C' = \frac{20 + 8 \frac{L}{R}}{20 + 19 \frac{L}{R} + 3 \frac{L^2}{R^2}} \quad (10)$$

and the resistance corresponding to it has been stated by equation (9).

The experimental results which are shown on the Figure represent confirmation of the Clausing correction factor within the experimental accuracy. The results shown have been selected so as to represent results obtained under conditions where the external resistance represented by the orifice or tube was sufficiently large so that the surface resistance of the solid did not enter. Those given by squares were obtained by direct comparison of a short tube $L = 1/8"$, with corresponding thin-edged orifices of equal radius. The uppermost square is within the experimental error of fitting the equation. It was obtained from two 2" diameter bottles, having 17 cm.² area of UCl_4 solid, in an experiment in which the temperature of the bottles was net equalized by a heat conducting block. The triangles represent points obtained from a study in which there was no corresponding thin-edged orifice. The points were fitted to the curve by assuming that the Clausing correction held for the point represented by $L/R = 3$. Points for L/R values less than 2 were obtained in the experiment but could not be used here since the control was not held mostly by the short tube. The small circles were obtained from tube flow calculations, the only points shown being those in which the molecular flow term exceeded 50%. These

216-31

DECLASSIFIED

circles can be construed as confirmation of the Clausius correction factor only through a fairly complicated argument. This has been given elsewhere (Ref. 2, Sec. 13, 34-36). The points shown represent the C' values which would be obtained from the actual experimental results with the tubes by application of equation (9), Ref. 2 with $F(P)$ set equal to 1, a molecular diameter of 5.6×10^{-8} cm. and with equation (5) for the vapor pressure. The experimental error is thus included in the C' results shown on the Figure.

Other short tube formulas do not represent the experimental results.

216-32
DECLASSIFIED

VII.

STUDIES MADE WITH THE CONTROL HELD BY THE SURFACE OF THE SOLID
AND IN WHICH THE TEMPERATURE IS HELD CONSTANT.

13. Introduction. The total amount of material which is transported from a plane surface of chemically pure material by sublimation into a vacuum is given by equation (3). The dependence on temperature is based directly on the vapor pressure equation of the solid, and the temperature which is required is the surface temperature of the solid. The effect of external resistances, of departures of the surface emissivities from unity, and the extent to which the surface temperature for a non-conducting solid departs from the radiator temperature, are adequately accounted for by the theory developed by Dr. MacWood. It is however, impossible to make experiments on granular UCl_4 correspond to the required conditions. The definition of surface area (section 3) becomes absurd as the particle size is increased. The definition of surface resistance, as defined by equation (2) is in need of revision, since all solids on which experiments could be made by us were contaminated by surface impurities. If the surface resistance is defined by multiplying equation (2) by $1/f$, f being no longer an accommodation coefficient as applied to pure solids but one made to account for the surface impurities for the inadequacy of the definition of the surface A_2 , the resistance becomes

$$W_2 = 2.5/A_2 f \text{ cm.}^{-2} \quad (12)$$

Last of all, no single assumption may be made with respect to the manner in which heat arrives at the subliming surfaces.

DECLASSIFIED

216-33

The experimental study on granular solids therefore retains its value on account of the need for arriving at rough values for the surface resistance, for determining surface temperatures in those temperature-pressure ranges in which there is marked surface cooling, and for making observations on the behavior of impurities.

PART A. TRANSPORTS ARE MEASURED.

14. Dependence on Impurities.

The only impurity of any consequence in the sublimation studies was the oxychloride, UOCl_2 . This is present at the surface of granular particles of solid UCl_4 from the reaction with water vapor. It also exists between the individual crystals (approximately 10 mesh at the largest) in the larger granules which were studied, having arrived there by being blown over from the UOCl_2 present in sublimers. In the case of the UCl_4 derived directly from UO_2 by the action of CCl_4 at 450° to 500° C. UOCl_2 is present inside the crystalline masses, usually not in excess of 3% in moderately coarse material and not in excess of 10% in fine material.

The effect of additional surface contamination by water vapor was studied experimentally. The UCl_4 aggregates were held in small containers, the nominal area exposed being 2.3 cm.^2 per sample. The amount of water reacting with each cm.^2 was determined in a dosage cell, and the amount of HCl given off was measured. Only a small fraction of the total HCl was given off in the dosage cell. The aggregates were exposed to water only on the upper surface. It was found in earlier work that in an uneven surface the projecting portions of granules remove most of the water from the air leaving the protected lower portions of the top surfaces essentially uncontaminated. -- The manner of water dosage was intended to correspond to the accidental contamination of the UCl_4 in charge bottles by water vapor.

DECLASSIFIED

216-34

The results are given in Table 4. It may be noted for all the materials except 10-fines, the effect of water contamination is not in proportion to the amount of water. For the 10-fines material there is some dependence on the amount of water vapor. Actually the results with this material should have shown a much more regular dependence on the amount of water contamination, but failed to do so on account of the slight differences in temperature between the positions which the individual samples occupied. This was the first work performed, (Exp. 2-15) and was never repeated, though it might have been desirable. The proportionate decrease in rate was largest for the 10-32 mesh samples, since this material was purer to start with and did not have the advantage of still larger particle sizes in avoiding the effect of water vapor.

The effect of impurities on the rate of well consolidated masses was shown in the study of two samples which were prepared by melting UCl_4 in stainless steel bottles of the same shape as were used otherwise. The amount of the surface impurity (which was UCl_3 in this case) was not measured, but the effect was marked. (See the diamond points, 430° set, Fig. 10)

It was hoped that the work with glass chips, and the 48 mesh beads, reported in section 8, would be useful as an artificial way of duplicating surface impurities. This has been reported in section 8 and Figure 4. The results obtained for 32-60 mesh and 32-fines material were not included in Figure 4 but are included in the following summary to show the surface resistance as dependent on impurity.

216-35

DECLASSIFIED

Set A. Exp. 23, 430° C.				Set B. Exp. 29, 410° C.		
Mesh of Material UCl ₄	UOCl ₂ %	Transports Uncovered	gm./cm ² /hr. 11.5mm of 2.2 mm. glass beads	Transports Uncovered	gm./cm ² /hr. 11mm. of 14-20 mesh glass chips (0.9mm)	
4-6	app. 3%	0.255	0.069	0.125	0.0192, .0185, .0178	
6-10	3.6	0.218	0.060	----	----	
10-32	3.0	0.185	0.049	0.076	0.0152, 0.0142, 0.0140, .0136	
32-60	5.8	0.110	0.049	----	----	
32-fines	6-8%	----	----	0.050	0.0162, .0160, .0157, .0150	

Care was taken to cover the samples with piles of glass which were equal in the different samples, and the resistance offered by the pile may be considered constant. In view of the size of the samples it is best to use the 10-32 mesh material as a standard. If this material is assigned a surface resistance of 1.0, the resistances for the 11.5mm set of glass beads is found to be 2.83 units, and for the 11 mm. thickness of glass chips 4.35 units. Then by comparison, the four different materials in Set A. have surface resistances 1.03, 1.05, 1.0, and 2.28 times as great as the 10-32 mesh, material, and in Set B 0.76, 1.0, and 2.05 times as great.

These results are about as one would expect them to be. The surface resistance for 4-6 mesh size material should be smaller than that for 10-32 mesh size material, for a given amount of impurity, as is shown in the next section. The resistance for the finer material should be higher.

Rather few experimental results with the horizontal apparatus (Figure 1) can be used to calculate f values, since external resistances as calculated from equations (2), (7), and (9) are too large to permit making a satisfactory estimate of f if the value is greater than 0.05. Early results obtained in Experiments 2-15 with Apparatus I (see Table 3) allow estimates

DECLASSIFIED

216-36

of the f values to be made as follows:

Material	% UOCl_2	f
10-fines	4.5	0.03 ± 0.01
10-32	3.0	0.08 ± 0.03
4-6	(3)	0.15 ± 0.05

It may be assumed that the f values at 430°C are no larger. The resistances equivalent to the f values provide ratios which agree approximately with those stated for the glass chip and glass bead covered samples.

15. Dependence on Particle Size.

When these studies were begun it was felt that particle size should have no effect, and this is very likely the case for pure UCl_4 . However, when impurities exist on the surface the particle size will affect the total area which is available for the production of gas. Therefore there should be some increase in transport as the particle size is increased. On the other hand, the UCl_4 which was employed was not of the same purity for the different particle sizes, even when taken from the same batch. The material of 10-32 mesh size had the least impurity. The impurity was not less in larger sizes, since the particles were then made up of the 10-32 mesh particles plus the UOCl_2 which was distributed throughout the mass during sublimation. Material finer than 32 mesh contained the UOCl_2 which flaked from the larger particles during screening, and so was less pure. This variation of impurity could not conveniently be eliminated in the study of particle size, and so the results of the two together must be shown. These results are given in Figure 7. The percentage impurity has been given

216-37
DECLASSIFIED

in section 14. In Figure 7 the solid-line curves represent the probable true particle size effect. It may be assumed, in keeping with Figure 3 that material of smaller size than 8-10 mesh does not possess a particle size effect. The heavy dashed lines represent the additional change caused by impurities. Experimental transports obtained from samples containing particles larger than 6 mesh are probably too small on account of small sample sizes. The points shown for Exp. 34 and 35 in Figure 7 were obtained from specially resublimed material graded to a rather narrow range in sizes. The material was first divided into lumps, 10-32 mesh, and 32-fines, and given non-volatile residue analyses. This resulted in values as follows: selected lumps had 1.37% UOCl_2 , the average lumps 3.5%, 10-32 mesh material 0.72% UOCl_2 , and the 32-fines 2.9% UOCl_2 . The 10-32 mesh material was then subdivided still farther, probably concentrating its impurity in the smaller size fractions, and a 32-35 mesh material was separated from the 32-fines group. The results for this group of samples alone are in keeping with the conclusions which have been made.

16. Dependence on the Experimental Temperature.

The dependence of the experimental transports for a given material on the temperature should be given by equation (4). This states simply that the transport is very nearly proportional to the vapor pressure as one changes from one temperature to another, since $T^{-1/2}$ does not change very much. It was felt that this equation should be tested in an elementary manner on various solids, and the results were obtained largely as a byproduct of other work. The results are shown in Figure 8. The dependence on temperature, and thus on vapor pressure, is rather near to that expressed

216-38

DECLASSIFIED

by equation (4). In this figure the transports are shown as their ratio to that calculated from equation (4), with $f = 1$, at various furnace temperatures. In order to obtain a test at the elevated temperature of 510°C , the glass covered samples were studied. Had these samples been uncovered the rate would have been much higher than the amount shown, at least until the UCl_4 was all sublimed.

The figure is also of interest in showing that the observed transports were all less than $1/12$ those which would have been predicted from equation (4).

It had been felt that the transport might not be proportional to vapor pressure on account of the relatively low transports which had been encountered, but deviations from proportionality with equation (4), with T defined as the furnace temperature, will be observed only when an appreciable surface temperature drop exists and when the effective surface area of the material is altered by mechanical removal of the solid impurities.

17. Experimental Results obtained on the Variation of the Transport with Time by the Weight Loss Method.

Changes in transport with time are brought about by changes in the effective area of sublimation, and by changes in the amount of surface impurity. The two together represent a change in surface resistance which should show up as the reciprocal of the change in transports.

The first study which was made on change with time (Exp. 17-22) was performed on 6-10 mesh sublimed UCl_4 of 3.6% UOCl_2 content. A series of six pairs of samples, the first 4 mm. thick, the second 8mm. and so on through 24mm. thick was prepared, and put through a short sublimation

216-39

DECLASSIFIED

Work was continued by the weight loss method through Experiment 33 with the object of quickly scanning the effect in uncovered samples of particle size on the decrease in transport rate with time, and of determining the effectiveness of piles of glass beads and chips in preventing the decrease with time. These results are given in Figure 10 in two parts, one for the samples studied at 430°C , the other with samples at 410°C . The experimental temperatures were slightly different, but were corrected to the two temperatures by assuming proportionality to vapor pressure. It may be first noted that all materials studied decreased in transport rate with time. Secondly it may be noted that the effect of removal of material on the transport rate was much greater if the particle size was smaller, and therefore the impurity larger for sizes under 10-32 mesh. Thirdly for the experiments with glass bead or glass chip cover it may be concluded that the glass cover continued to remove part of the difference between the different solids, but that the effectiveness of it decreases as the impurity at the solid surface piles up. This should have been the case, since the glass pile offers a constant external resistance while the surface resistance of the solid is increasing more rapidly for the fine material than the coarse material, and the control of the process should gradually revert to the solid. The alteration of resistance ratios may be calculated from these effects.

18. Studies made with a Vacuum Balance on the Variation of the Transport with Time as a function of several Geometric Factors.

Studies with a vacuum balance were undertaken to obtain more complete histories on the behavior of granular aggregates under different geometric conditions and to demonstrate one method of retaining control

216-41
DECLASSIFIED

run at 410°C to remove HCl , and to help select the samples which would be assigned to each set. The sample of each pair which gave the slightly lower rate was assigned to set II, and this sample was then shaken vigorously, properly stoppered, in the dry box. The remaining six samples were assigned to set I and were disturbed as little as possible. Shaking of the one set was intended to remove the surface impurities to the bottom of the sample. The samples were then taken through as many as five successive equal runs at 430°C , those of set II being shaken at the end of each run. The transport rates were then compared. The shaken set, except for the samples which were too thin, gave the same or higher rate in successive runs until the impurity, which was of a fluffy nature, allowed the remaining UCl_4 to be imbedded in it. The rate then decreased. The unshaken set showed a rapid decrease in transport rate, demonstrating the effect of the building up of the impurities. The result obtained with one pair is shown in Figure 9, the horizontal lines showing the number of grams removed per run, dashed vertical lines showing the starting point, the heavy solid and dot-dash line showing the actual rate for sample I and the average rate for sample II respectively, and the light dot-dash lines showing the probable actual rate for sample II in each of the runs. The solid line I, of Figure 9 is also shown as the dot-dash line in the 430°C portion of Figure 10. These results were used at the time to propose that the charge bottles in Calutron units be supplied with some sort of shaking device. The experimental results showed that the impurity could be readily removed by tumbling the mass, but that it otherwise stayed as a sort of filamentous replica of the whole particle which once was located there.

216-40
DECLASSIFIED

over the sublimation rate.

The vacuum balance apparatus as used in Experiments 2, and 12-15 is shown in Figure 11 and the description is largely given in the legend accompanying the figure. With this apparatus it was possible to determine changes in length of the spring with an accuracy of ± 0.01 cm., or 0.2 gm. The capacity of the balance was about 600 grams, and thus it permitted the study of fairly large samples. With this improved apparatus the sample temperature was measured directly.

The vacuum balance used in experiments 1, 3, 4, and 6 was similar to that shown in Figure 11 but did not maintain constant position of the sample container, U, with respect to the furnace, S. The Wilson Seal assembly, B, and C, was not used, and the spring was fixed at the upper end. A pointer fixed to a rod at the lower end of the spring allowed satisfactory measurement of the spring displacements. Motion of the sample container, U, was made up for periodically by raising the furnace. This apparatus was more awkward to use than the improved model, but it gave satisfactory results. The temperature of the sample would have been obtained in Experiment 1, except for a short in the thermocouple. Since the thermocouple leads had to be made part of the spring, subsequent use of the thermocouple in Experiments 3, 4, and 6 was abandoned.

For both apparatus, the sample containers were filled and the assembly of the apparatus was made in a dry-box mounted on top of the furnace. After the apparatus had been assembled and evacuated, the final alignment was made, and initial scale readings were taken. The furnace temperature was then raised, and, when a constant value was reached, observations were started, the spacings of the observations being determined by the rapidity of sublimation.

216-482
DECLASSIFIED

At the completion of an experiment, dry carbon dioxide was admitted to the apparatus, and this was then taken apart. The condensate on the support rod, R, was weighed. The nature and condition of the remainder of the sample was noted, and the contents were weighed and in some cases separated by screening to determine the quantity of fine material which was left.

When the apparatus was left overnight, as it had to be for some of the experiments with low transport rates, the temperature was left at the experimental level, if the rate was low enough, but was otherwise dropped to some lower level, and the values obtained for the overnight rate were converted to rates at the experimental temperature by assuming the rates at both temperature to be proportional to equation (4). Other temperature variations were accounted for similarly.

The sample containers were of stainless steel, 2" in diameter, and 2.5 to 4" in length. The screens and cages were of pure nickel. The screens had open areas totalling 46% of the area covered, and were either 20 mesh, with 0.016" wire or 16 mesh with 0.020" wire.

The experimental schedules and conditions are summarized in Table 5. The sample container assemblies are shown in the lower half of Figure 12.

The order in which the work was undertaken was dictated by the hope that the effect of the piling up of impurities (Section 17) could be avoided by utilizing geometries in which the sample surface lay in vertical directions. It was also hoped that the UOCl_2 impurities would fall through the screens which were used to retain the charge. After this was tried, it was hoped that better results would be obtained with a sample which faced downwards. Surely the impurities should fall off, and in

216-43

DECLASSIFIED

order to make this possible the screen was handwoven to the bottom of the cage to leave fairly large openings ($1/8$ " squares) and a net open area of about 80%. When this failed it was decided that sample assemblages which would become more open with time (Exp. 4) should be tried, and a fairly good rate history was observed, but not as good as was expected. Therefore it was decided to resort to a control method which would unquestionably work, the application of an orifice for control; the self-opening geometry of Exp. 4 was used so that an orifice of fairly large diameter could be employed ($11/32$ "). It had been hoped all along that it would not be necessary to apply orifice control to obtain satisfactory transport rate histories. With Exp. 6 the main study was finished, but it was still felt that something should be learned about the geometries which had been used in earlier rate-time histories (Section 17), and therefore four experiments were made on samples in which the sample surface face upwards.

The transport rate-vs. time histories are shown in Figure 12 as the change in the transport rate from the initial rate as a function of the fraction of the total sample contents which were sublimed. It was the intention to study transport rates primarily at 430°C , but this policy had to be abandoned in favor of temperature adjustment to obtain a satisfactory initial rate.

Experiment 1 showed a more rapid decrease in transport rate than had been hoped for. This was caused by the failure of the impurity to fall off through the screen. The transport rate was fairly good until about 40% of the material was sublimed, at which time the stainless steel block which "rode" on the charge (so as to keep removal of the vapor from the

216-44
DECLASSIFIED

sides) suddenly dropped to a lower level, and the rate fell simultaneously. The experiment was terminated on account of fogging of the scale.

Experiment 2 was intended to show better control than Experiment 1 and a more constant transport rate. In starting the experiment the initial temperature of 432°C was found to be too low for satisfactory rate measurements and therefore, after 16% of the contents had been sublimed the temperature was raised to 456°C . The values at the lower temperature, and the initial rate, were adjusted to the new temperature. Subsequently the transport rate rose for an appreciable length of time, then fell off rapidly on account of sample rearrangement (though this was not observed directly as in Exp. 1), and subsequently decreased about as was to be expected.

Experiment 3 was intended to show a nearly constant transport rate, and much to our surprise, after dropping slowly for 10% of the contents sublimed the rate rapidly decreased to half the value and by the time only 25% of the contents had been sublimed, the rate had decreased to less than 35%, subsequently falling to 20% of the original rate before the experiment was terminated. This experiment left no doubt about the fact that the impurities had their effect regardless of position.

Experiments 4 and 6 have already been partly explained, and the results were about as expected. The rate-time history for a geometry such as was used in Experiment 4 is not at all unsatisfactory, since it can be used to obtain a constant transport rate during the sublimation of 80% of the contents with a gradual temperature increase of only 15°C . As shown in the diagram, the UCl_4 was located on screens, in $3/8$ " layers, separated by screens, and walled by screens. The experimental geometry for Experiment 6 was identical to that of Experiment 4.

2/6-45

DECLASSIFIED

For the geometries in which the charge faced upwards, the work was started in Experiment 12 with material containing fine UCl_4 of fairly high purity, but it was still expected that the rate would fall off rapidly with time. The experimental temperature was first set at 451°C , with the solid temperature at 443°C . The transport rate for the whole sample was only 3.5 gm./hr. and it remained fairly steady for about three hours and then rapidly fell to almost zero. This behavior is shown by the dot-dash curve (12) in the Figure. So by the time 16 gm. had been removed (8% of the contents) there was no need to continue the study at this temperature. Therefore the temperature of the furnace was raised to 513°C , as rapidly as possible, and after a short period of low transport rate the transport rate rose rapidly to a value of 35 gm./hr. with a temperature of the solid of 487° . It was soon observed that impurities were being ejected from the sample container and were collecting like icicles on obstructions vertically above the sample container. The weight connected with these impurities must have been very small however. The transport rate gradually rose to a maximum of 50 gm./hr. at which time the temperature of the thermocouple inside the solid mass indicated only 458°C . The rise in the rate must have been accompanied by formation of a dome-shaped surface for the aggregate. The temperature drop of the solid from 487 to 458°C merely represents the fact that the colder subliming surface was coming close to the thermocouple. The transport rate was studied until it had fallen to 8 gm./hr.

In experiment 13, 6-8 mesh material of 3.1% UOCl_2 content, showed a reasonably high rate at 452°C (solid at 448° to 439°). The sample was studied to almost complete exhaustion. The flattening out of the rate to a value of about 45% of the initial rate during the latter part of the

DECLASSIFIED

216-46

sample history may be partly accounted for by the increase in surface area which results as the material close to the wall of the sample container is sublimed away. This was accompanied by the drop of the temperature of the solid to 439° , a temperature which must have been nearly that of the subliming surface.

Experiment 14 on 8-10 mesh material was of very short duration (15% of the content sublimed) and was terminated on account of a short in the jacket thermocouple. It was repeated in Experiment 15, showed the same history during the first 15%, and was continued to 55% sublimation of the contents. The study then was terminated since it was desired to inspect the sample before the evidence of dome formation was lost. The material at the surface was found to be consolidated into a truncated cone, and about one-half of the sloping areas were free of non-volatile surface coverings. This dome formation was accompanied by a temperature drop of the mass to 442.5°C , during the experiment.

The non-volatile content of the material in each experiment has been given in Table 5. The effects of these small non-volatile contents have been shown by the records taken to be rather large, except in those instances where the surface covering is mechanically removed (temperature of the solid exceeds 450°C) or its effect is otherwise avoided.

Experiments 12-15 provide the best opportunity in all these studies for stating probable values of f for the solids used. In these experiments the resistance through which the gas had to flow after leaving the sample was rather small, and therefore the surface resistances have a considerable effect on the transport. The temperature measurements also allow one to make reasonable estimates of the surface temperature of the solid. In

216-47
DECLASSIFIED

order to make the calculations, the initial rate measurement is taken, and the lowest observed temperature of the solid mass is taken as applying to this initial rate, though the probable initial surface temperature may have been still lower. The value of f which is then obtained may be considered to be a lower limit, the true value lying between this lower limit and a value which would at most be twice as large. The calculated f values are:

Exp.	Material	$\% \text{UOCl}_2$	f
12	8-fines	2.8	0.03 at 451°C furnace temp.
12	8-fines	2.8	0.9 at 513°C furnace temp.
13	6-8 fines	3.1	0.07 at 452°C furnace temp.
15	8-10 fines	(3)	0.08 at 452°C furnace temp.

The values obtained with the furnace set at about 450°C are in agreement with those estimated for different sublimed material in section 14. The rapid increase of the calculated f value to nearly 1 for the 8-fines material in Exp. 12 is in agreement with the observations made concerning the removal of the non-volatile UOCl_2 .

216-48
DECLASSIFIED

PART B. TEMPERATURES MEASURED

19. Methods and Apparatus in the Measurement of Temperatures.

The distribution of temperatures within a solid mass during sublimation was measured directly. It had been hoped at first that it would be possible to obtain simultaneous measurements of sublimation rates, but this could not be done.

The apparatus used is shown in Figure 12; it was readily adapted to use in temperature studies by the use of the brass disc, P. The mercury cups were removed. The vacuum balance extension of the apparatus was removed and was substituted by a glass dome bearing a suitable flange. The sample cage shown in the figure was substituted by one of the two arrangements shown in Figure 13.

A preliminary experiment had been performed in which it was shown that glass covered thermocouples were completely unsatisfactory, since they indicated wall temperature and not the temperature of the solid. Bare thermocouples were therefore used. Those used in Experiment A. were 26 gauge iron-constantan, and were located as shown in Part A. of Figure 13. Though subject to such corrosion that the thermocouples were good for only one experiment, they gave satisfactory temperature readings until the resistance of the thermocouple circuit was doubled. The resistance of the couples was repeatedly checked. A more satisfactory thermocouple was found to be the 28 gauge chromel-alumel couples used in subsequent experiments, the wires being joined together with silver solder. In Experiments B, C, and D these couples were distributed as shown in Part B of Figure 13. The wires of each couple were separated by fine porcelain tubing and were led out through a nickel column. The silver solder had to be replaced between experiments. In Experiments C and D thermocouple 18 was sub-

216-49
DECLASSIFIED

stituted by a calibrated 36 gauge Pt-Pt+10%Rh thermocouple so as to make sure that the corrosion of the silver solder was introducing no thermal effects. It was thereby found that the thermocouples were all giving valid temperature readings. The radiation baffles at top and bottom were necessary for definition of temperatures but offered an external resistance which undoubtedly lowered the transport rates.

The furnace used throughout the studies was an 18" one instead of the 12" one shown in Figure 11.

The thermocouples were all placed near the axis of the sample containers and lay in planes perpendicular to the axis of the containers for distances not less than 3/4 inch. Conduction along the wires did not result in errors of temperature measurement.

The sample material was graded for size, and the container was filled to a depth so that the upper thermocouple was from 1 to 3 mm. under the top surface. The total thickness was 75-80 mm. Approximately 300 gm. of material was used in each container.

The UOCl_2 content of each sample was between 2% and 3%.

20. Experimental Results.

The observed temperatures were tabulated and the thermocouple differences were largely eliminated by setting all values equal at some lower temperature, usually 250°C or 350°C. This involved a maximum correction of 3°C and an average correction of 0.5°C to the observed results. The corrected results are given in Table 6, and are shown in the order, left to right, in which the experiment was conducted. The temperature differences are the differences from thermocouples 7 and 22. The values

216-50
DECLASSIFIED

listed represent conditions as near to steady state in each case as it was possible to arrange. All such temperature data change as the sample material is removed. This is shown by the distribution of temperatures in Table 6B at 486°C and 502°C, in Table 6C by the 434°C measurement at the end, and in Table 6D by the 434°C set. The values shown in Tables 6B-D, excepting the 434°C values for Experiments C and D are shown in Figure 14 in the order from top to bottom of coarse sample material to fine.

At the end of each study the apparatus was examined. After Experiment A, thermocouple 1 was 8 mm. above the solid surface, but thermocouple 2 was still covered. After Experiment B nothing could be learned since the solid was completely sublimed before being disassembled. After Experiment C thermocouple 11 was still covered but the material immediately about it was non-volatile. After Experiment D thermocouple 11 was covered by a small amount of non-volatile matter, and the upper sample material was separated from the bottle wall for a short distance.

From the temperature data in Table 6 it is possible to construct pressure gradient curves through the solid mass. This gradient is not as sharp as we had thought earlier, but the curves are in harmony with the observation that there is a good deal of transport of material within the granular mass, which has its final result in consolidating the mass in a compact form. This transport is naturally a part of the heat transfer mechanism.

Some of the observations on temperature drop reported in section 18 are of real interest, since these are correlated with the measurement of transport rates. These will be discussed later.

2/6-51

DECLASSIFIED

21. The Maximum Temperature Drop Brought About by Sublimation.

From the results in Table 6 and Figure 14, combined with observations made at the time the apparatus were disassembled it is possible to arrive at fairly good estimates of the maximum temperature drop encountered in the region within which the removal of the gas from the solid mass was occurring. The estimates are stated in Table 7, and the temperature drops greater than 2°C are shown in Figure 15. By referring to the table one may observe that the temperature drop is either slight or non-existent at 380°C , then grows fairly rapidly and subsequently less rapidly. There is rather little difference between the material of 4-6 mesh and that of 8-10 mesh. The material containing UCl_4 of 10-fines size has a very low temperature drop until the wall temperature exceeds 460°C . This material then rapidly changes to give the same evidence on temperatures as was given by the larger-sized material. This can only be accounted for by the mechanical removal of the overlying impurities by the vapor "wind" (See Exp. 12, Section 18).

In Figure 15 the experimental results on the temperature drop are compared with the theoretical values calculated both from equation (6) (Table 2) and from MacWood's Theory (Ref. 3b). It may be shown that radiation ceases to be the only important factor in the process of bringing heat to the surface at about 430°C , and therefore the theories should be tested, or fitted, at the lower temperature end. It is clear that both treatments

216-52
DECLASSIFIED

lead to the conclusion that the coarse solids are behaving as though the transport is restricted to somewhere between 0.25 and 0.1 of the amount which corresponds to equation (4). It may thus be concluded that the effective f value is somewhere between 0.25 and 0.1 for the coarse solids. The effective f value for the 10-fines solid, from Table 2, is approximately 0.015 at temperatures below 460° . At the higher temperature it possesses a value which is somewhat greater.

For use in Figure 15 the results calculated from MacWood's paper have been brought in line with the present value for the vapor pressure curve and the corresponding heat of sublimation, and the curves shown are therefore different than those shown in a previous report.

With the comparison made at the lower temperature, it is clear from Figure 15 that the results at higher temperatures depart markedly from the radiation theory, and this is to be expected, since the transfer of heat through the solid by motion of material eventually becomes more important than the receipt of heat by radiation, and since the resulting compacting of the solid increases the ordinary thermal conductivity of the mass at those faces which remain in contact with the container. Due to the rapid performance of these experiments the contact with large areas of the walls of the sample container was not lost.

DECLASSIFIED

216-53

VIII. STUDIES MADE WITH THE CONTROL HELD BY THE SURFACE OF THE SOLID AND IN WHICH THE EXPERIMENTAL TEMPERATURE WAS ABRUPTLY ALTERED.

22. Description of the Method and the Experimental Schedule.

Studies of transport rates and temperatures as a function of the amount of radiant energy applied directly to the surface were made with a modification of the apparatus shown in Figure 12. An 18" long furnace was used throughout, and the experimental arrangement within the furnace tube was altered as shown in Figure 16. In this figure the main diagram shows the arrangement which was used in the measurements of transports, and for these the vacuum balance attachment shown in Figure 12 was used. For the temperature studies the mercury cups were retained but the balance was disconnected and thermocouples were connected as shown in the lower part of Figure 16. The samples of UCl_4 were retained behind a $3/4$ " diameter nickel screen (46% open, wire diameter 0.020", 16 wires to the inch) and had an average thickness of 13 mm. The height of the solid was about 3.5 inches. The upper part of the solid was covered with two radiation baffles, and the bottom of the container had several radiation baffles. These prevented loss of heat in longitudinal directions. The external radiation baffles were connected to the container support at the top and were located about 1 inch below the container at the bottom. Temperatures of the baffle closest to the container were measured. The sample container was furnished with a 7" nickel filament, laid out in a single long loop, which was used to supply radiant energy directly to the surface of the sample. Thermocouple 1 was soldered directly to the screen, 2 was located 1 mm. back, 3 was located 2 mm. back, 4 was located 5 mm. back, and 5 was located about 1 mm. from the bottle wall. The sixth thermocouple was soldered to the inside of

216-54
DECLASSIFIED

the bottle wall. The stainless steel container was split horizontally so as to permit assembly of the thermocouples and inspection between runs. The wattage applied to the system was controlled through a small variable transformer, the amperage and voltage were measured, and the resistance of the system was checked independently, so that the wattages might be stated with reasonable accuracy.

The experimental schedule is given in the following summary.

Studies of Transport Rate

- VB-5. 6-8 mesh UCl_4 . 138 out of 272 gm. sublimed.
Schedule: 430°C , 3.4 watts; 3.4 watts, repeat; 1.7 watts; 7 watts.
- VB-10. 6-8 mesh UCl_4 . 135 out of 264 gm. sublimed. Repetition of VB-5 but with the power leads taken out through the mercury cups, which were not used in VB-5.
Schedule: 421°C , 3.4 watts, 1.5 watts, 6.5 watts.
 450°C , 3.7 watts, 1.5 watts, 6.9 watts.
- VB-11. 10-fines UCl_4 . 39 grams out of 312 sublimed. Like VB-10.
Schedule: 423°C , 2.7 watts; 425°C , 1.0 watts, 5.2 watts.

Studies of Temperatures.

- Preliminary Studies: VB-7, VB-8 6-8 mesh UCl_4 , $400-430^\circ$, 2, 5, 11 watts.
VB-9, 10-fines UCl_4 , 425°C 2, 5, 11 watts.
- TS-4. 10-fines UCl_4 . 98.8 gm. out of 273 sublimed.
Schedule: 248°C , 1.4, 5.8 watts; 425°C , 1.4, 3.4, 5.8 watts
 450°C , 1.4, 5.8 watts; 250°C , 5.8 watts;
 350°C , 5.8 watts; 403°C , 5.8 watts; 452°C , 5.8 watts
 498°C , 5.8 watts.
- TS-5 6-8 mesh UCl_4 . 117 out of 217 grams were sublimed.
Schedule: 250°C , 5.8 watts; 350°C , 5.8 watts; 400°C , 5.8 watts
 422°C , 1.4, 3.4, 5.8 watts (Same schedule here as VB-10)
 453°C , 1.4, 3.4, 5.8 watts; 499°C , 5.8 watts,
 250°C . 5.8 watts.

The non-volatile impurity for the above solids was between 2% and 3% UOCl_2 .

DECLASSIFIED

216-55

As can be surmised from the statement of the amount sublimed in each experiment, the geometry of the charge did not remain identical throughout the experiment, nor even the particle size. The material gradually moved away from the screen and toward the walls, in the direction in which heat had to be transported. The uncertainties resulting from this migration were, however, diminished by reserving to the last the work at the highest temperatures.

To assure adequately fast temperature measurements, the key of the galvanometer was pressed down and the deflections to new positions were noted as a master switch to all the thermocouples was rotated. Six readings were usually completed in less than 20 seconds. The temperatures were measured to within 0.2°C , and are correct on an absolute scale to better than 2°C . The resistance of each thermocouple was taken into account in interpreting the deflection measurements, else the method of reading the temperatures would have been inaccurate.

23. Experimental Results on Temperatures.

These experiments were conducted in such a way that both the response to thermal changes and the steady state temperatures attained were measured. All the observations were plotted graphically and were carefully examined for consistency, and these graphs were then used to obtain the final values of the temperatures which were involved.

One of the 32 temperature response records is given in Figure 17. The temperature response curves enabled us to determine the time-lags between various maxima and minima, such as furnace temperature variations, so the conclusions would be free of these effects.

The temperature response as a function of wattage is not shown in any figure. It was observed that up to six watts the temperature changes were approximately proportional to the wattage, but the proportionality breaks

RECEIVED

2/6-54

down whenever the difference in temperature is large. This follows directly from the Stefan-Boltzman Law and from observations on the nature of thermal conductivity within the solid.

Temperature response as a function of temperature and for a constant wattage is shown for both 10-fines and 6-8 mesh UCl_4 in Figures 18 and 19. In Figure 18 the temperatures shown are those for thermocouple 1, the screen thermocouple, and in Figure 19 for thermocouple 4, which was 5 mm. back of the screen. The curves for the thermocouple 4 all show a small time lag. It is clear that the curves for $250^{\circ}C$ and $350^{\circ}C$ are all similar. The $400^{\circ}C$ curves for the fine material are more nearly like those at $350^{\circ}C$ than like the $500^{\circ}C$ curves, but for the coarse material the resemblance is closer to the $500^{\circ}C$ curves. The implications of these measurements on thermal conductivity are taken up in the next section.

The steady-state temperature (as would be represented by plateaus in Figures 17 to 19) were determined in each of the temperature studies and are shown graphically in Figure 20. The temperature drop of the subliming surface, which was the subject in Sections 20 and 21, is also shown in these results for the different geometry employed, and the alteration with the change in the characteristics of the solid mass brought about by the application of radiant energy is shown best in the extreme left and right figures. It may be noted that the effect of the experiment on the condition of the solid mass was proportionately greater for the finer material. The temperature drop is shown by the lower solid and dotted lines. The upper solid and dotted lines represent the steady state temperature attained with the application of 5.8 watts to the surface. The curves for the $500^{\circ}C$ experiment are interesting in that they show the existence of the region of greatest sublimation rate to be about 3-5 mm. back of the screen, which would be within the upper 2mm of the solid itself, owing to the backing away from the screen.

DECLASSIFIED

216-51

24. Conductivity of the Granular Aggregates.

The changes in conductivity of the granular aggregates, which may be qualitatively observed in Figures 18 and 19, may be measured from the steady state temperatures shown in Figure 20. The results on the 10-fines material are most representative, since they correspond more nearly to solids in actual use. For this solid, and for the conditions within the mass as they existed at the time, the conductivities are as follows:

Mean Temperature °C	Conductivity Watts per inch thickness per sq. in. per °C
288	0.00316
376	.0044
423	.0057
440	.0076

Conductivities can hardly be determined with certainty from the data at 440°C or at higher temperatures, on account of the heat lost by the sublimation of UCl_4 .

If it is assumed that the changes in conductivity come about by the greater effectiveness of the radiation transfer per °C (this doubles in changing from 288 to 440°C), then the differences in conductivity as the temperature is changed from 288 to 423 °C are completely accounted for, and the radiation phenomena, including heat transfer by radiation directly through the solid, represent the primary mode of heat conductivity.

As has been pointed out before, however, there are other forms of conduction. These are conductivity through solid particles, which may be ruled out in the experiments described above, conductivity of the gas itself, which likewise is very small, and conductivity resulting from the evaporation of material from a warmer surface and condensation on a colder surface. The heat transfer represented by equation (4), by difference

DECLASSIFIED

216-58

in the G values per degree, with $f = 1$, is as follows.

Conductivity by Transfer of UCl_4

Temp.	Watts/°C/sq. in for one pair of surfaces
400	0.035
420	0.1
440	0.26
460	0.61
480	1.4
500	3.0

It is clear from these numbers that the heat transfer by transfer of UCl_4 would be the important mechanism at 400°C, if the effective f equals 1. However, the transfer is interfered with by impurities and by resistance of the apertures, so that the heat conductivity by this method probably becomes significant only at 420°, important at 440°C, and dominant at 480°C and above. The manner in which the temperature drop which could have been attained by sublimation if the heat is received by radiation alone is lessened by the transfer of material is clearly shown by the experimental points given in Figure 15. A temperature drop of 30° was observed when one would have expected 50°, at 470° surface temperature, which may be accounted for by assigning 40% of the heat transfer to the material transfer mechanism.

25. Experimental Results on Transports and on the Correspondence of the
Transports with Temperatures.

The experimental results on transport rates with and without added radiant energy are shown in Figure 21 by means of the solid lines. The correspondence of these transports with the temperatures observed in the

DECLASSIFIED

216-59

temperature studies is shown by the essential agreement of the solid lines with the dotted lines. These dotted lines represent the temperature curves converted into transports by the use of equation (4), assuming that the temperature change altered the rate of sublimation by the ratio of two values obtained from equation (4), any difference in wattage between the corresponding studies being first removed by setting temperature proportional to wattage. These studies definitely show that the change in transport rate and the temperature alteration agree.

IX. SOME PRACTICAL CONSEQUENCES OF THE WORK.

26. Practical Consequences.

It was mentioned in preceding sections that the studies originated in a practical question and then proceeded along lines which were dictated by what could be seen of the role which the studies could play in proper use of UCl_4 in Calutron units.

The deficiency of the early mechanical valves in Calutrons was satisfactorily explained by the work on control with orifices, and this work led to many important results. It was discussed in detail with Mr. J. G. Dorward Jr., together with the results of the vacuum balance studies, and resulted in his development of the thermal valve as a replacement for the mechanical valve. Difficulties were later encountered in the application of this valve to fairly impure UCl_4 , due to the clogging of

DECLASSIFIED

216-60

the gas passage by UOCl_2 which was apparently blown there from the surface of the subliming masses and was cemented in place by CrCl_2 . This difficulty was largely overcome, however, by proper design of the gas passage. Later orifice valves were designed in which the size of the gas passage was altered by passing electric current through a stout coil which was part of the valve, and which, in the magnetic field, operated satisfactorily.

The work on temperatures was done in cooperation with the development of UCl_4 charge bottles for Calutron units in which the change in rate of transport was to be accomplished by rapidly altering the surface temperature of the solid by means of radiant energy. These radiant heater bottles were quite successful, when compared with the means of control formerly employed, but they did not compete with the thermal valve design which was soon brought in. The radiant energy bottles would have been more successful had the temperature differences been larger. For proper operation such a charge bottle would be dependent on conditions such as pertain only at temperature approaching 500°C . At a temperature the surface temperature lowering is sufficiently large so that radiant energy applied to the surface can be used to alter transports without long-time thermal effects, but at this temperature, where the application of radiant energy can satisfactorily bring about two to four-fold changes in transport rates, the transport rates are already so high as to make it necessary to close down the openings in the charge bottles and thus make radiant energy control less useful. The design was most successful in allowing rapid alteration of transport rate within the practical limits imposed by the

DECLASSIFIED

216-61

temperature phenomena, but major changes in transport rate still had to be accomplished by alteration of the temperature of castings which surrounded the charge bottles.

The experimental studies resulted in a better basis for the construction and operation of the large sublimers. Several test runs were made with the 30 Kg. sublimers (Ref. 5c), in which it was shown that introduction of suitable baffles to reduce the amount of UOCl_2 which was blown over, and opening up of the solid mass by using trays, and screen shelves, resulted in much better UCl_4 . If one wishes to sublime UCl_4 in such a way as to free it of UOCl_2 , probably the best way would be to utilize a vessel which is essentially enclosed, except for a vacuum pumpout, place the charge in the lower half of the container and allow it to condense on the walls of the upper half of the container by maintaining a temperature of about 470° in the bottom reservoir and 450 to 455°C in the top reservoir. It was frequently observed in the use of 9 Kg. charge bottles in Calutron units, that this slow sublimation and condensation frequently resulted in large masses of fairly pure UCl_4 . Rather rarely were these so located as to be more effective on account of their greater purity, however. In one instance in these experiments (Exp. 3, Section 18) such a sublimers was set up. The upper cap of the vessel employed was covered by a $1/4"$ thick deposit of pure UCl_4 , which appeared to have been devoid of any UOCl_2 .

DECLASSIFIED

2/6-62

Acknowledgements.

The experimental studies which were used as the basis of this paper were made by Miss Iva Streeter, Mrs. Merle Estabrook, Mr. P. H. Davidson, and the author. The materials were supplied by Mr. Roy Krohn. The encouragement and advice of Dr. C. H. Prescott, Jr. and Dr. G. E. MacWood are gratefully acknowledged.

216-63

DECLASSIFIED

TABLE I

VALUES CALCULATED FROM THE VAPOR PRESSURE
EQUATION

Temp °C	P mmHg	G gm/hr/cm ²
360	0.000618	0.101
370	0.00113	0.182
380	0.00202	0.323
390	0.00356	0.565
400	0.00615	0.971
410	0.0105	1.64
420	0.0176	2.74
430	0.0291	4.49
440	0.0474	7.27
450	0.0762	11.6
460	0.121	18.3
470	0.190	28.6
480	0.295	44.0
490	0.452	67.0
500	0.684	100.7
510	1.026	150.1

2/6-64

DECLASSIFIED

TABLE II

SURFACE TEMPERATURE DROP
(all energy received by
radiation)

$f =$	1	0.5	0.25	0.1	0.05	0.025	0.01	0.005
T_{oc} (wall)	Surface Temperature Drop, °C							
360	2.3	1.2	0.62	0.25	0.13	0.065	0.026	0.013
380	5.7	3.3	1.7	.73	0.36	0.19	0.076	0.036
400	11.7	7.3	4.2	2.0	.92	0.5	0.21	0.10
420	20.	14.	8.8	4.5	2.4	1.3	0.52	0.26
440	30.	23.	16.	8.8	5.2	2.9	1.2	0.62
460	43.	34.	25.	15.	9.8	6.0	2.7	1.4
480	57.	46.	36.	24.	16.	11.	5.5	3.0
500	72.	58.	48.	35.	26.	18.	10.	6.0
520	83.	70.	60.	47.	37.	27.	16.	10.

DECLASSIFIED

2/6-65

93-718

TABLE III
Experimental Conditions in the Studies with the Horizontal Apparatus

Experi- ment No.	Type of Study	Appara- tus	Experimental Temp. °C	Time Hrs.	Gm. HCl Collected	No. of Samples	Total Area of Solid A ₂ cm ²	Total Area Exposed cm ²	Minimum Area for escape of Gas A ₂ , cm ²
1-15	A,C	I	450	2	—	4	9.2	¹² 9.2	33
16	B,C	IIa	446	2.1	1.06	12	26	26	7
17	B,E	IIa	408	1.58	.64	12	26	26	7
18	B,E	IIa	427	a.74	.108	12	26	26	7
19	B,E	IIa	427	2.64	.084	12	26	26	7
20	B,E	IIa	432	2.80	.090	12	26	26	7
21	B,E	IIa	426	2.74	.048	12	26	26	7
22	B,E	IIa	426	2.95	—	12	26	26	7
23	C,E	IIa	429	2.82	.135	12	26	20.5*	7
24	C,E	IIa	427	2.69	.014	12	26	20.5*	7
25	C,E	IIa	426	3.3	.159	12	26	17.6*	7
26	C,D,E	IIa	426	3.42	.003	12	26	17.6	7
27	B,C,D	IIa	412	3.87	1.00	12	26	25.*	7
28	B,C,D,E	IIa	411	4.06	.076	12	26	25.*	7
29	E,F	IIa	406	3.66	.053	12	26	13.*	7
30	D,E,F	IIIb	502.5	1.25	0	6	13	6.5*	7
31	E,F	IIIa	408	3.72	.014	12	26	13.*	7
32	E,F	IIIa	409.5	4.61	0	12	26	13*	7
33	E,F,G	IIIa	414	4.11	.054	12	26	12.5*	7
34	B,F	IIIa	429	3.16	.041	10	23	19	7
35	G	IIIa	431	2.97	.257	9	22	2.5	7
36	E,H	IIIa	430	5.78	.005	6	15	.05	7
37	E,H	IIIa	429	5.89	0	6	15	.05	7
38	J	IIc	431.5	3.2	.116	4	69	4.7	12.5-33
39	J	IIc	427	2.2	.027	2	34.4	3.8	12.5-16
40	J	IIc	430.5	3.1	—	1	17.3	.6	16
41	J	IIc	430	2.4	.115	3	52	6.6	12.6-16
42	J	IIc	432	8.0	—	3	52	.32	12.5-16
43	J	IIc	432	2.8	.176	2	63	5.0	12.5-16
44	J	IIc	433	2.16	.009	2	63	2.2	12.5-16
		IIIa	430	5.3	.054	11	27	11.1	7
	J	IIIb	494	2.95	.130	8	18.8	.72	7
47	J	IIIb	466	2.09	.164	8	18.8	.72	7
48	J	IIIb	389	21.9	.002	8	18.8	.72	7
49	J	IIIa	388	17.3	.027	8	18.8	.72	7
50	J	IIIa	359.5	19.5	.007	8	18.8	.72	7
51	J	IIIa	357	45.9	.0102	7	16.9	.29	7
52	J	IIIa	421.5	4.4	0	7	16.9	.29	7
53	J	IIIa	359	38.5	.012	7	16.9	.29	7
54	J	IIIb	468.5	2.47	.015	7	16.9	.29	7

Types of Study

- A. The Effect of Surface Contamination by Water.
- B. The Effect of Thickness
- C. The Effect of Particle Size
- D. The Effect of Temperature
- E. Changes with Time
- F. The Effect of Screens, Layers of Glass Chips
- G. Transport through orifices 1/8" Thick
- H. " " " thin edged. Choice of materials. of construction
- J. " " " Vapor Pressure

Apparati

- I. First apparatus, using a vertical tube, 33 cm.² area inside, 12 inch. furnace and containing four samples. The samples were first arranged without a temperature equalizing block, but later a copper block was made to contain the four samples. Finally a brass shell, 1/8" thick, was used outside the glass furnace tube to equalize temperatures. Results obtained with these various arrangements of the apparatus are to be regarded as being obtained under less well-defined thermal conditions than later studies. The thermocouple in all cases was located in the axis of the apparatus.
- IIa. Apparatus shown in Figure 1. Twelve samples set in 2.5" diameter truncated nickel-plated copper block, 6" long, with axial hole for thermocouple. The furnace tube cross-section was 33 cm.², the area above the block, 7 cm.². Maximum sample area was 26 cm.². The brass shell was used. No radiation baffle.
- IIb. Same as IIa, but with a light-weight hollow replica of the internal copper block, made of thin sheet copper, for rapid heating and cooling.
- IIc. Apparatus shown in Figure 1, without radiation baffle. Samples contained in 2" diameter stainless steel bottles set on their sides. Maximum of four samples. First sample pumped out through 33 cm.² cross-section, those behind it through 12.5 cm.² cross-section.
- III a,b,c. Same as IIa,b,c but with the radiation baffle system shown in Figure 1 included. The area for passage was 16 cm.² for each half-baffle. The baffle was made of thin sheet copper or sheet nickel.

The vacuum system for all apparati was adequate.

TABLE IV
SURFACE CONTAMINATION BY WATER

Gm. Sublimed	Added Water mg/cm ²	Gm. Sublimed	Added Water mg/cm ²
(1) <u>Single Lumps</u>		(4) <u>10-fines</u>	
5.47	0	1.236	0
4.66	0	1.671	0
5.76	0	1.713	0
5.16	0	1.503	0
4.06	0	1.612	0
6.36	0	1.887	0
Ave 5.2		1.222	0
4.73	7	1.554	0
4.41	11	Ave. 1.54	
		1.217	1.5
(2) <u>4-6 Mesh Particles</u>		0.785	2.8
3.67	0	0.832	4
4.14	0	1.258	4.25
5.74	0	1.368	4.25
4.66	0	0.785	8
Ave. 4.55		1.053	10.8
3.12	7	0.589	19
3.74	7½		
5.58	7½		
5.21	10		
(3) <u>Mesh Particles</u>			
3.78	0		
2.68	0		
3.44	0		
1.80	0		
Ave. 2.95			
1.80	7		
2.04	11		
1.57	23		
1.93	24		

DECLASSIFIED

67
2/6-65A

TABLE V

Experimental Conditions in the Studies with the Vacuum Balance Apparatus

Exp. No. = →	1	2	3	4	6	12	13	14	15
UCl ₄ , mesh size	6-8	4-8	4-8	6-8	6-8	8-fines	6-8	8-10	8-10
Furnace Temperature, °C	430-40	432-456	439-41	431-6	450	451-513	452	452.5	452.5
Screen Temperature, °C	----	426-442	----	----	----	487	----	----	----
Temperature of Solid, °C	Shorted	422-437	----	----	----	443 to 458	448-39	447	447.5
Diameter of Charge, inches	1-3/8	1-3/8	1-7/8	1-3/8	1-3/8	1-7/8	1-7/8	1-7/8	1-7/8
Height or Thickness, inches	3	3	2-1/4	3	2-3/4	2-3/8	2-3/4	2-3/4	2-3/4
Surface Area, A ₂ , cm ²	84	84	17.7	82	87	17.8	17.8	17.8	17.8
Area for Escape of Gas, cm ²	22.5	6.4	17.7	22.5	0.596	9.6	9.6	9.6	9.6
Wt. of UCl ₄ , gm	170.6	169	187.6	175.8	165.2	195.4	253.4	226.9	232.6
Sublimation by balance, gm	76	130	109	151	155	183	233	----	129
Condensation on balance support, gm	----	10	8	9	7	7	12.5	----	10
% NVM (UOCl ₂)	(3)*	1.9-3	(3)*	3.3	2.9	2.8	3.1	----	(3)*

* Estimated from other measured results

TABLE VI

Temperature Drop during Sublimation. Experimental Values

A. (4-6 mesh)					
Wall Thermocouple, #7 °C	393	419.4	430.7	476.1	495.2
Thermocouple No.	Temperature Difference, °C				
1	-2	-2.2	-3.6	-4.5	+2.8
2	-2	-3.9	-7.4	-14.5	-13.7
3	-1	-2.5	-3.7	-8.7	-13.2
4	0.5	-0.7	-1.7	-4.3	-4.2
5	0	-1	-1.4	-4.7	-4.7
6	0	-1	-1.7	-4.7	-5.2

B. (10-fines)						1/2 hr. later		1/2 hr. later
Wall Thermocouple, #22 °C	350	394	417	451	477	486	496	502
Thermocouple No.	Temperature Difference, °C							
11	.6	-.5	-.4	-.4	-3.8	-2.6	-2.8	-1
12	.2	-.5	-.4	-.8	-13.6	-20.2	-24	-22.7
13	.4	-.2	2	.2	-8	-17.6	-25.4	-29
14	1.0	-.5	2	2.6	-4	-10.8	-17.4	-22.7
15	.6	-.5	2	2.8	-1.4	-5.4	-12.2	-16.8
16	.5	-.5	1.9	3.8	Burned out			
17	.5	-.5	1.9	3.8	-.5	-2.5	(-10.5)	Burned out
18	.5	-.3	2.1	3.8	0.9	1.7	0.9	-.9
19	.7	-.6	2	4	0.8	3	1.6	1.3
20	-.1	+.1	2.2	4	1.4	2.7	2.7	2.2

C. 4-6 mesh (repeat)									
Wall Thermocouple #22, °C	240	380	412.5	443	454	467.5	485.5	434	237
Thermocouple No.	Temperature Difference, °C								
21 (upper wall)	0	0.5	-0.5	-1.5	-0.5	1.5	2.5	1	0.5
23 (Furnace)	6.5	9	9.5	10	11.5	12.5	16	9	7
11	0	-2	-6.5	-9.5	-10	-9	-8.5	-4	0
12	0	-.5	-2.5	-8.5	-10.5	-13.5	-21.5	-5.5	.5
13	0	1	-.5	-5	-7	-9	-16.5	-5	1
14	0	0	-1.5	-4	-4	-6	-12.5	-4	1
15	0	0	+.5	-4.5	-2.5	-2.5	-6	-5.5	----
16	0	1	-.5	-3.5	-1	-2.5	-7	-1	.5
17	0	0	-.5	-3	0	-1	-3.5	-1	1
18	0	0	0	-2	0.5	-1	-4.5	-1	1
19	0	0.5	+.5	-1	1.5	2	-1	0	1
20	0	0	.5	-1.5	1	.5	-1	-1	.5

D. (8-10 mesh)									
Wall Thermocouple #22, °C	240	415.5	338.5	440	457.5	467.5	487.5	434	234
Thermocouple No.	Temperature Difference, °C								
21 (upper wall)	0	-.5	0	0	-.5	-1	-1	-1/2	0
22 (Furnace)	6	9	7	10.5	10.5	13.5	15.5	9	6
11	0	-4	.5	-3	-4.5	-4.5	-5	-2	0
12	0	-5	.5	-8.5	-12	-14.5	-27.5	-1.5	0
13	0	-2	1	-4	-6	-7.5	-21.5	-8.5	0
14	0	-1	1	-3	-4.5	-6	-15.5	-5.5	---
15	0	0	---	-1	-3	-1.5	-8.5	-4.5	0
16	0	-.5	1	-.5	-1	-1	-4.5	-.5	0
17	0	-.5	.5	0	-.5	-.5	-2.5	0	0
18	0	1.5	.5	.5	-.5	0	-1.5	0	0
19	0	2	1	2	1.5	2.5	0	1	0
20	0	2.5	.5	1.5	1.5	2.5	1	1	0

TABLE VII

Estimated Maximum Temperature Drop during Sublimation

A. (4-6 mesh)			D. (8-10 mesh)		B. (10-fines)	
Wall °C	Temp Drop °C		Wall °C	Temp. Drop °C	Wall °C	Temp. Drop °C
340	0				350	0
393	2.5				394	0
419	5.5		415	4.5	417	1
431	9		440	12	451	3
476	15		458	16	477	16
495	18		467	19	486	24
			488	30	496	29
C. (4-6 mesh)			434	11	502	33
380	2.5					
412	6.5					
443	11					
454	13					
467	16					
485	22					
434	6.5					

DECLASSIFIED

216-30

FIG 3 I
HORIZONT. APPARATUS

- A 18" Hevi-Duty Furnace, connected with Foxboro Controller, thermocouple in the slot of the brass tube, K
- B 69 mm. diameter Pyrex tubing, approximately 26" long, 65 mm. internal diameter, with flange
- C Radiation baffle, 16 cm.² clear passage
- D 63 mm. diameter nickel-plated copper block, flat top, with twelve recesses for sample containers
- E Sample containers.
- F Glass tubing inserted into block, containing thermocouple
- G Asbestos and magnesia packing
- H Taper seal, sealing wax
- J Thermocouples, iron-constantan or chromel alumel
- K Brass tube, 1/8" wall, with slot for thermocouple

FIGURE II

Dependence of Transports on Thickness of Samples

○ 6-10 mesh, 450°C Exp. 16	◻ 4-6 mesh, 410°C Exp. 27
□ 32-60 mesh, 450°C Exp. 16	◻ 4-6 mesh, 410°C, second heating Exp. 28
△ 6-10 mesh, 410°C Exp. 17	○ 10-32 mesh, 410°C Exp. 27

216-7R

FIGURE III

MINIMUM THICKNESS OF SAMPLE
REQUIRED FOR NEARLY MAXIMUM TRANSPORT

The horizontal line indicates
the range of particle sizes
in the sample studied.

DECLASSIFIED

216-725

GRAPHICAL SUMMARY
EXPERIMENTAL RESULTS OBTAINED
FOR THE TRANSPORT THROUGH
GLASS BEADS AND CHIPS

Experiments at 430°C: ○ 2.9 mm. beads, 4-6 mesh UCL₄, Exp. 22
 □ 2.2 mm. beads, 4-6, 6-10, 10-32 mesh UCL₄, Exp. 23
 △ 1.25mm. chips, 10-22 mesh UCL₄, Exp. 25
 ◇ 0.9 mm. chips, 10-22 mesh UCL₄, Exp. 25
 Experiments at 410°C: ◇ 0.9 mm. chips, 4-6, 10-32 mesh UCL₄, Exp. 29
 ○ 0.0295 mm. beads, 4-6 mesh UCL₄, Exp. 27
 All ratios of $G_{obs.}/G_2$ obtained by direct comparison of the covered
 samples with uncovered samples in the same experiments.

FIGURE V
CONTROL OF TRANSPORT BY ORIFICES

△ 490°C, Exp. 46

□ 470°C, Exp. 54

□ 470°C, Exp. 47

○ 430°C, Exp. 36-37, Low

values from partial clogging

○ 430°C, Exp. 38-44.

$A_2 = 17 \text{ cm.}^2$

○ 430°C, Exp. 45

○ 430°C, Exp. 43-44.

$A_2 = 46 \text{ cm.}^2$

△ 425°C, Exp. 52

◇ 390°C, Exp. 48

◇ 390°C, Exp. 49

○ 360°C, Exp. 50, 53

□ 357°C, Exp. 51

A_2 equals 2.43 cm.^2 for each sample
except as indicated

DECLASSIFIED

216-75

FIGURE VI

Correspondence of the Transport of UCl_4 Gas through Short
Tubes with the Clausing Formula

Circles: See text

Squares: Exp. 36, 37, 42, 430°C , 4-8 mesh Harshaw UCl_4 .

Triangles: Exp. 35, 430°C , 14-20 mesh sublimed UCl_4

LEGEND: Refer to the Text.

DECLASSIFIED

DECLASSIFIED

216-75

DEPENDENCE OF THE TRANSPORT ON PARTICLE SIZE

□ Exp. 34 (light line corresponds to these points).
 ◊ Exp. 19. ◻ Exp. 39. △ Exp. 27.

○ Exp. 23.
 ▽ Exp. 28.

◊ Exp. 16.
 ◻ Exp. 35.

DECLASSIFIED

DECLASSIFIED

216-7B

FIGURE VIII

Dependence of the Transport on the Vapor Pressure

○ 4-8 mesh, Harshaw material
Exp. 19, 38, 39, 43, 47, 50

□ 32-60 mesh, sublimed
Exp. 16, 23, 27

◇ 6-10 mesh, sublimed
Exp. 16, 17, 27

Samples covered with 1.34

gm./cm.² glass chips of 14-20 mesh

△ 4-6 mesh, sublimed

○ 10-32 mesh, sublimed

▽ 32-60 mesh, sublimed

DECLASSIFIED

DECLASSIFIED

214-78

FIGURE IX

COMPARATIVE STUDY OF SHAKEN AND UNSHAKEN SAMPLES

FIG. X
DECREASE IN TRANSPORTS WITH TIME

DECLASSIFIED

DECLASSIFIED

216-77-80

FIGURE XI
VACUUM BALANCE APPARATUS

216-89

INDEX FOR FIGURE XI
VACUUM BALANCE APPARATUS

- A₁-A₄ Counterbalanced support and locking device for the furnace
- B "Wilson" seal, with attachment for coarse and fine adjustment of the spring
- C Standard Taper, sealed with sealing wax
- D Centering tripod
- E Pointer, fine and flat
- F Scale. Magnification device attached to the outside of the tube not shown.
- G Steel spring, 100 turns of 0.031" diameter wire on 0.3" radius
Sensitivity for different springs, 15-20 gm./cm.
- H Pyrex tubing, 70 mm. i.d., 30" long, with ground flange
- I Alignment clamps and rings, with three cork-tipped screws each
- J Detection device. Buzzer, light, or deflection meter.
- K Spring extension, nickel, 0.06"
- L Contact plate, ground flat and turned so that its surface was vertical to rod K.
- M Brass disc, equipped as the base for the balance. The pump-out hole was 0.25" in diameter and was closed when not in use by a small fitting attached to K which centered in the hole and carried a small rubber washer. The disc was also equipped with three pointed rods which served to provide electrical contact with L.
- N Pyrex tubing connection unit. H, M, and N were sealed with rubber washers and stopcock grease. Air pressure served as a suitable clamp.
- O 1" i.d. connection to vacuum system.
- P Water-cooled electrical connection disc. Brass. Equipped with 12 holes, each containing porcelain insulators, sealed with porcelain cement, sealing wax, and glyptal varnish. Space for ten thermocouples, and two power leads used directly or through mercury cups. The disc was itself equipped with a thermocouple to measure its temperature. The upper seal was made up with a rubber washer and stopcock grease. The lower seal was made up with sealing wax.
- Q Furnace tube, 65 mm. i.d. Pyrex tubing; tubes ranged from 15" to 30" long.
- R Support rod, shown with 1/8" porcelain thermocouple tubing with connectors dipping into mercury cups, but also used with 1/16" nickel wire instead.
- S 12" or 18" Hevi-Duty furnaces, 3" i.d. Resistance of the two halves equal.
- T 1/8" wall Brass tube, serving as temperature equalizer. Thermocouple soldered to it.
- U Sample container.
- V Furnace tube support.

916-87

FIGURE XII.
EXPERIMENTAL STUDIES OF THE VARIATION OF TRANSPORT WITH TIME AS OBTAINED BY MEANS OF A VACUUM
BALANCE.

Scale Drawings of the Container Geometries

Exp.	1	2	3	4	6	12	13	14, 15
UCl ₄ mesh	6-8	4-8	4-8	6-8	6-8	8-fines	6-8	8-10
UCl ₄ grams	170	169	188	176	165	195	253	226, 233
Furnace T. °C	430-40	456	439-41	431-6	450	513	452	452
Initial Transport, gm./hr.	15	11.5	7.0	14.5	5.0	37.	6.1	7.1

216-810

FIGURE XIII
TEMPERATURE STUDY APPARATUS

216-86

216-854

FIGURE XIV

TEMPERATURE LOWERING AS A FUNCTION OF POSITION, MATERIAL, AND TEMPERATURE

FIGURE XV
MAXIMUM TEMPERATURE LOWERING

UCl₄ mesh: Δ 4-6. ∇ 4-6 repeat. $\circ$ 8-10. $\square$ 10-Fines

Curves: — MacWood Theory, and — complete elementary theory, both with the transport assumed restricted to 0.25 of the maximum value; - - - MacWood Theory, and - - - complete elementary theory, both with the transport assumed restricted to 0.1 of the maximum value; $\cdots$ elasticity assumed to be 1.

216-85

FIGURE XVI

RADIANT ENERGY APPARATUS

Figure XVI
RADIANT ENERGY APPARATUS

- A Porcelain insulator and support
- B Mercury cups
- C Radiation baffles
- D Hanger
- E Radiation baffles
- F Connection to nickel filament
- G Nickel filament
- H Nickel screen, 16 mesh, 46% open area
- J Stainless steel container 28 ga. chromel-alumel thermocouples, insulated with fine porcelain-tubing

216-87

FIGURE XVII
TYPICAL TEMPERATURE RESPONSES
(Exp. VB-9, 10-fines, 2-watt)

(Note: Thermocouple 7, the bottom baffle, usually was very nearly the same as thermocouple 6, on the bottle wall)

FIGURE XVIII

TEMPERATURE RESPONSE

Response as a function of temperature, 5.8 watts; Screen Thermocouple
 --- 10-fines UCl_4 (TS-4) ——— 6-8 mesh UCl_4 (TS-5)

Temperature Rise as
 Galvanometer Deflection
 (1 div. = approx. $2.5^\circ C$)

48-912

FIGURE XIX

TEMPERATURE RESPONSE

RESPONSE AS A FUNCTION OF TEMPERATURE, 5.8 watts. Screen Thermocouple 5 mm. back of nickel screen

--- 10-fines UCl_4 (TS-4) --- 6-8 mesh UCl_4 (TS-5)

Temperature Rise as
Galvanometer Deflection
(1 div. = approx. $2.5^\circ C$)

12.9.18
18.5

FIGURE XX

STEADY STATE TEMPERATURES. EXP. TS-4, TS-5

Screen
Wall

UC1 mesh 10-fines TS-4
UC1 450° curve a little later n
UB1 mesh 6-8 TS-5
Upper Curve 5.8 watts through filament
Lower Curve 0 " " "

92

FIGURE XXI

CORRESPONDENCE BETWEEN TEMPERATURE AND VACUUM BALANCE STUDIES

Transport rates calculated from temperature studies TS-4, TS-5
Observed rates, in vacuum balance studies, VB-10, 11
Assumed base rates

16-916