UNCLASSIFIED

CF-55-4-72(Del.)

OAK RIDGE NATIONAL LABORATORY
Operated By
CARBIDE AND CARBON CHEMICALS COMPANY

UCC

POST OFFICE BOX P
OAK RIDGE, TENNESSEE

DATE: April 11, 1955

SUBJECT: 25 PROCESS ASSISTANCE
For Period of March 21, 1955 to April 1, 1955

F. L. Culler

Photostat Price \$ 1.80

Microfilm Price \$ 1.80

Available from the
Office of Technical Services
Department of Commerce
Washington 25, D. C.

LEGAL NOTICE

This report was prepared as an account of Government sponsored work. Neither the United States, nor the Commission, nor any person acting on behalf of the Commission:

A. Makes any warranty or representation, express or implied, with respect to the accuracy, completeness, or usefulness of the information contained in this report, or that the use of any information, apparatus, method, or process disclosed in this report may not infringe privately owned rights; or

B. Assumes any liabilities with respect to the use of, or for damages resulting from the use of any information, apparatus, method, or process disclosed in this report.

As used in the above, "person acting on behalf of the Commission" includes any employee or contractor of the Commission to the extent that such employee or contractor prepares, handles or distributes, or provides access to, any information pursuant to his employment or contract with the Commission.

UNCLASSIFIED

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency Thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

DISCLAIMER

Portions of this document may be illegible in electronic image products. Images are produced from the best available original document.

OAK RIDGE NATIONAL LABORATORY
OPERATED BY
CARBIDE AND CARBON CHEMICALS COMPANY
A DIVISION OF UNION CARBIDE AND CARBON CORPORATION

2

UCC

POST OFFICE BOX P
OAK RIDGE, TENN.

April 11, 1955

~~SECRET~~

-3-

1.0 25 PROCESS ASSISTANCE

1.1 1A Column Chemistry

Work is continuing on the organic emulsion problem under 1A column feed-plate conditions. Application of variations of the Thorex head-end treatment, i.e., dehydration of feed impurities by high temperature digestion at high nitrate concentrations, has been studied using an emulsion-producing 2S Al bar-stock dissolver solution (1.8 M Al , 1 M H^+ , 0.008 M Hg^{+2}) as the LAF. These experiments are summarized in Table 1. The results indicate that 3 hours digestion at the boiling point in the presence of 8 M HNO_3 at Al concentrations of 2 to 4 M, prior to readjustment to LAF flowsheet conditions, will prevent organic emulsion formation. The treated LAF's (unfiltered) were batch-equilibrated for 1-1/2 minutes with 6% TBP-Amsco in the presence of neutral $0.75 \text{ M Al(NO}_3)_3$ - $0.02 \text{ M Fe(NH}_2\text{SO}_3)_2$ scrub, using the volume ratio AF:AS:AX = 100:20:40, and the presence or absence of stable emulsions noted. Apparently the presence of H^+ ion during digestion is necessary for the dehydration, since digestion of $\sim 5 \text{ M Al}$ with essentially no acid present (see Experiment No. 3, Table 1) did not eliminate emulsion formation. In all other runs, a clear aqueous phase was obtained in 20 to 30 seconds and the organic cleared in 65-80 seconds, leaving a clean interface.

An attempt was made to produce emulsion by adding trace impurities to synthetic feed. This feed was batch equilibrated with 6% TBP-Amsco in the presence of $0.75 \text{ M Al(NO}_3)_3$ - $0.02 \text{ M Fe(NH}_2\text{SO}_3)_2$ - 3.0 M HNO_3 scrub solution with the feed:scrub:solvent volume ratio of 100:20:40. Trace impurities (Fe, Mn, Cu, Ni, Ag, V, Ca, Mg, Si) in the same concentrations as determined by spectrographic analysis of 2S Al bar-stock were "spiked" into the system one at a time and the phase disengagement times noted after such addition. Although some variation of disengagement time was seen, no stable emulsions were produced by this method. Therefore, it was concluded that the impurities known to be present in the bar-stock must exist in different forms in actual dissolver solution.

1.2 0.75" Diameter Pulsed Column Facility

1.21 Batch Dissolution of Dummy Fuel Elements

Dummy fuel element #D-99 (2350 grams total weight) was dissolved in 50 liters of 7.4 M HNO_3 containing $0.005 \text{ M Hg(NO}_3)_2$. The reaction was initiated by heating to 90°C , and then controlled by applying cooling water for about 1 hour. Steam was then reapplied to maintain the dissolver at $\sim 105^\circ\text{C}$. Table 2 shows the results of periodic sampling, and indicates that the element was essentially completely consumed within a period of about 2 hours or less.

~~SECRET~~

DECLASSIFIED

~~SECRET~~

-4-

Table 1

Feed-Al bar-stock dissolver solution:

1.8 M Al
1.0 M HNO_3
0.008 M H^+

Standard equilibration test for emulsion:

50 ml of designated LAF
10 ml neutral 0.75 M $\text{Al}(\text{NO}_3)_3$ - 0.02 M $\text{Fe}(\text{NH}_2\text{SO}_3)_2$
as LAS
20 ml of 6% TBP-Amsco as LAX
Equilibrate 1-1/2 minutes

Experiments No.	Dissolver Solution Pretreatment	Observations
1	Evaporate to 1/4 vol.; add equal vol. 16 M HNO_3 ; digest 3 hr. Evaporate off acid (142°C) and readjust to 1.0 M H^+ and 1.8 M Al.	No stable emulsion
2	Evaporate to 1/2 vol. (130°C) add equal vol. 16 M HNO_3 ; digest 3 hr. Evaporate off acid (130°C); add equal vol. of 2 M HNO_3 : $\text{H}^+ = 2.3 \text{ N}$, Al = 1.8 M.	No stable emulsion
3	Evaporate to 1/3 vol. (135°C), digest 3 hr. Add back condensate: H = 1.0 M, Al = 1.8 M.	Obtained stable emulsion
4	Evaporate to 1/2 vol. (130°C); add equal vol. 16 M HNO_3 ; digest 3 hr. Evaporate off acid (130°C); dilute back to original volume with H_2O : H = 1.0 M, Al = 1.8 M.	No stable emulsion

(Note: In all cases a clear aqueous phase was obtained in 20 to 30 sec.; with the exception of Experiment No. 3, a clear organic phase was obtained in 65-80 seconds.)

Table 2

Dissolution of Dummy XXXXXXXXXX Fuel Element in 7.4 M HNO_3 -0.005 M $\text{Hg}(\text{NO}_3)_2$

~~SECRET~~

-5-

1.22 Flowsheet Testing

To date, three column runs were made utilizing feed prepared by dissolving dummy [REDACTED] fuel elements, digesting, filtering, and spiking with fission products from irradiated U-Al alloy. Runs HCU-1 and HCU-2 were of 7 hours duration and Run HCU-3 lasted 11 hours. The following flowsheet conditions were used:

1AF/75 ml/min = 3.8 g U/l, 1.0 M HNO_3 , 1.8 M $\text{Al}(\text{NO}_3)_3$, 0.005 M $\text{Hg}(\text{NO}_3)_2$, $1.5 - 5.0 \times 10^7$ Gross β c/m/ml, $3.4 - 8.1 \times 10^7$ Gross γ c/m/ml.

1AX/30 ml/min = 6% TBP in Amsco Special Naptha No. 1

1AS/15 ml/min = 0.75 M $\text{Al}(\text{NO}_3)_3$, 3.0 M HNO_3 , 0.02 M $\text{Fe}(\text{NH}_2\text{SO}_3)_2$

1BX/11 ml/min = 0.01 M HNO_3

Results of run HCU-1 (AF = 1.5×10^7 Gr β c/m/ml) indicated that the A column had reached equilibrium with respect to the fission products at the end of about 5 hours (~ 6.5 volume changes), and that the B column had reached equilibrium at the end of about 6 hours. The Gross β decontamination factor (D.F.) across the A column was about 2×10^4 , and about 8×10^4 across both columns; the Gross γ DF across both columns was 1×10^4 .

Table 3 shows decontamination data from Run number HCU-2 (AF = 2.5×10^7 Gr β c/m/ml).

Table 3

First Cycle Decontamination - Run No. HCU-2

F.P. Activity	1AF, c/m/ml	1BP, c/m/ml	DF
Gross β	2.47×10^7	4.08×10^3	2.57×10^4
Gross γ	9.42×10^6	7.40×10^3	5.33×10^3
Ru β	1.38×10^6	148	3.91×10^4
Zr γ	1.81×10^6	2.3×10^3	3.29×10^3
Nb γ	3.62×10^6	2.4×10^3	6.32×10^3
TRE β	1.53×10^7	$< 10^2$	$> 10^5$

Results of Run HCU-3 confirmed these decontamination factors on a feed having about twice the gross activity of that in HCU-2. The decontamination factors for Gross β and Gross γ activities were 3×10^4 and 5×10^3 , respectively. Results of individual fission product decontamination are not presently available.

Column operation was very smooth throughout all runs, and essentially no interfacial material or emulsions built-up during the operation.

~~SECRET~~

DECLASSIFIED

~~SECRET~~

-6-

1.3 Mixer-Settler Facility

An excessive amount of difficulty with the Zenith metering pumps, caused by corrosion of internal parts (made of Type 400 stainless steel) in contact with TBP in Amsco, necessitated frequent shutdowns and repairs. All solutions in contact with the pumps have been changed to either water or straight Amsco in an effort to keep the pumps operating.

Pump failures ruined the tracer level run that had been started in the mixer-settler unit. Another run is scheduled for 3-28-55.

2.0 METALLEX

2.1 Reduction of ThCl_4 with NaHg

Experiments were continued in which ThCl_4 powder was reacted with NaHg in glass apparatus at temperatures ranging from ~ 130 - 230°C using pitched blade agitators and no baffling in the system. Analytical results of these experiments show ~ 80 - 90% reduction of ThCl_4 to Th quasi amalgam based on analysis of acid and water wash solutions, in experiments carried out about 160°C . In one experiment a maximum temperature of 153°C was recorded and a low conversion of ThCl_4 to thorium amalgam of $\sim 25\%$ was found.

Other experiments were carried out by W. Schaffer in which a small Abbie "Dispersall" mixing unit was used as a reactor. This unit may be described as containing a mixing device somewhat similar to a coffee mill. It provides a high shear to the reactants and may be operated at variable speeds. Analysis of reactants from the initial run using this equipment while operating at a temperature range of ~ 25 - 145° , and containing 195 gm Th as ThCl_4 produced a good grade of quasi amalgam with a yield of $> 50\%$ ThCl_4 reduction to Th amalgam. Incomplete analysis of later runs show this apparatus to be well suited to production of thorium quasi amalgam on a scale of the order of $\sim 1/2$ to 1 lb. Th per run.

~~SECRET~~

DECLASSIFIED

~~SECRET~~

-7-

Reduction of ThO_2 by NaHg

Experiments were carried out in an attempt to react ThO_2 (produced by thermal decomposition of $\text{Th}_2(\text{C}_2\text{O}_4)_2$ at 650°C) with NaHg, without success. The reactants mixed extremely well, and visually appeared as the reactants did when ThCl_4 is used in place of ThO_2 . However, on washing the amalgam or dry filtering to separate the bulk of the Hg, no quasi or Hg containing Th was found. Likewise, the usual black thorium-mercury compound was not observed. Runs with ThO_2 prepared at lower temperatures, as well as dried $\text{Th}_2(\text{C}_2\text{O}_4)_2$ and ThOCl_2 , are planned.

2.2 Metal Quality Studies

Samples of metal prepared by arc-melting sintered compacts showed the following properties:

Table 4

Component	Sample 1	Sample 2	Sample 3
ThO_2 , by HCl-insoluble	0.58%	0.76%	0.59%
HNO_3 -HF insoluble	0.45%	0.40%	0.35%
Oxygen by vacuum fusion	480 ppm	1220 ppm	420 ppm
Nitrogen by vacuum fusion	225 ppm	330 ppm	190 ppm
Nitrogen by Kjeldahl	150 ppm	330 ppm	190 ppm
Carbon	400 ppm	440 ppm	430 ppm
Hydrogen by vacuum fusion	8.2 ppm	13.0 ppm	7.8 ppm
Iron	1200 ppm	650 ppm	1100 ppm
Mercury	21 ppm	17 ppm	9 ppm
Sodium	12 ppm	<10 ppm	<10 ppm
Annealed density	11.67	11.65	11.63
Hardness as cast, R_B	10, 10, 12	34, 34, 32	7, 11, 13
Hardness as annealed, R_B	<0, <0, <0	24, 25, 26	3, 6, 2

All properties except iron content are within target specifications as set up by the Quality Working Committee on Thorium Specifications (DPST 54-582) Nov. 1954. It is of interest to note that chemically, the only significant differences which might account for the higher hardness of sample no. 2 are oxygen and hydrogen.

A study of possible reasons for spalling and cracking of sintered compacts showed that impurity contents of ThO_2 below 3.0%, sodium below 100 ppm, carbon, nitrogen, hydrogen and mercury in the quantities encountered prior to arc melting could not account for this type of behavior. Sodium ranged between 30 and 240 ppm; ThO_2 between 1.0 and 3.9%; Hg between 4 and 730 ppm; carbon between 210 and 790 ppm; nitrogen 72-310 ppm; hydrogen, 4 to 80 ppm. Sodium content above 100 ppm and ThO_2 above 3.0% appeared to increase cracking of sinters.

~~SECRET~~

DECLASSIFIED

~~SECRET~~

-8-

2.3 Phase Study of the Thorium-Mercury System

Studies of the thorium amalgams indicate that the ThHg_3 hexagonal close packed phase is stable at elevated temperatures (about 200°C) in the presence of free mercury. At room temperatures in the presence of free mercury a new phase appears which is identified by its X-ray diffraction pattern. This new phase (phase II) exhibits intense diffractions of the $\text{Cu K } \alpha$ X-rays at Bragg angles of 14.0° , 17.5° and 29.0° . This phase II forms slowly and becomes observable when the amalgam has been at room temperature for several days. Also phase II is the only solid phase found in amalgams which had been formed by low temperature reductions, 50°C .

Studies of the amalgam from the pressing step following filtration of the amalgam indicate that as the thorium concentration increases from 4 to 15% the amount of the ThHg_3 hexagonal close packed phase increase and the amount of the phase II decreases.

~~SECRET~~

DECLASSIFIED