~~CONFIDENTIAL~~

~~SECRET~~
JUL 30 1962

UNCLASSIFIED

ATOMICS INTERNATIONAL

A Division of North American Aviation, Inc.

MASTER

CFSTI PRICES

H.C. \$ 1.00; MN .50

Classification cancelled (or changed to)

~~CONFIDENTIAL~~

notice from Atomic International
by authority of dated March, 1966

by J.C. Ridenour TISOR, date 3-9-66.

Do not remove
this sheet

Facsimile Price \$ 6.80
Microcard Price \$ 1.85
for Access Permittees
Available from the
Division of Technical Information Extension
P. O. Box 1001
Oak Ridge, Tennessee

NAA-SR-MEMO

This document contains 16 pages

This is copy 27 of 33 series A

~~RESTRICTED DATA~~

THIS DOCUMENT CONTAINS RESTRICTED DATA AS
DEFINED IN THE ATOMIC ENERGY ACT OF 1954.
ITS TRANSMISSION OR THE DISCLOSURE OF ITS
CONTENTS IN ANY MANNER TO AN UNAUTHORIZED
PERSON IS PROHIBITED

~~SECRET~~

Security Classification

This document contains Secret-Re-
stricted Data relating to civilian
applications of atomic energy.

NAA-SR-MEMOs are working papers and may be expanded,
modified, or withdrawn at any time,
and are intended for internal use only.

AEC RESEARCH AND DEVELOPMENT REPORT

This report may not be published without the approval of the Patent Branch, AEC.

RELEASED FOR ANNOUNCEMENT
IN NUCLEAR SCIENCE ABSTRACTS

LEGAL NOTICE

This report was prepared as an account of Government sponsored work. Neither the United States, nor the Commission, nor any person acting on behalf of the Commission:

A. Makes any warranty or representation, express or implied, with respect to the accuracy, completeness, or usefulness of the information contained in this report, or that the use of any information, apparatus, method, or process disclosed in this report may not infringe privately owned rights; or

B. Assumes any liabilities with respect to the use of, or for damages resulting from the use of information, apparatus, method, or process disclosed in this report.

As used in the above, "person acting on behalf of the Commission" includes any employee or contractor of the Commission to the extent that such employee or contractor prepares, handles or distributes, or provides access to, any information pursuant to his employment or contract with the Commission.

~~GROUP I~~
~~Excluded from Automatic~~
~~Downgrading and Declassification~~

UNCLASSIFIED

~~SECRET~~

CONFIDENTIAL

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency Thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

DISCLAIMER

Portions of this document may be illegible in electronic image products. Images are produced from the best available original document.

UNCLASSIFIED

~~CONFIDENTIAL~~

ATOMICS INTERNATIONAL A Division of North American Aviation, Inc.		NAA-SR-MEMO- XXX NO 6532	APPROVALS
TECHNICAL DATA RECORD		PAGE 1 OF 16	
AUTHOR J. D. Watrous	DEPT. & GROUP NO. 793-35	DATE 6/26/61	
		GO NO 7560	
TITLE Properties of SNAP 4 Materials		S/A NO 2415	RECOMMENDED FOR OUTSIDE DISTRIBUTION ☒ YES ☐ NO
		TWR 21928	
PROGRAM SNAP 4	SUBACCOUNT TITLE Fuel Process Development		SIGNATURE
DISTRIBUTION USE AN ASTERISK (*) TO INDICATE THOSE WHO ARE TO RECEIVE COMPLETE COPIES	STATEMENT OF PROBLEM <p>Diverse sources of information are available concerning properties of SNAP 4 materials. A compilation of this information into a concise form would be of considerable benefit to personnel involved in the SNAP 4 program.</p>		
D. F. Atkins S. J. Cina M. V. Davis T. F. Edziak L. M. Flower L. E. Fort J. L. Grimaldi M. V. Haberer B. E. Harper D. L. Henry V. Keshishian J. R. Lewis D. A. McGee M. E. Nathan D. H. Platus H. E. Richter W. J. Roberts J. L. Shapiro M. H. Slater J. F. Stolz R. R. Turk W. D. Wallace J. D. Watrous C. E. Weber J. R. Wetch R. O. Williams C. C. Woolsey	ABSTRACT <p>SECRET</p> <p>Pertinent physical and mechanical properties of Zr and Zr-U hydrides have been abstracted from recent publications from General Electric-Aircraft Nuclear Propulsion Department, Denver Research Institute, Battelle Memorial Institute, General Atomics, National Bureau of Standards, and Atomics International. Similar data on stainless steels were obtained from the Metals Handbook, 8th Edition. This information is presented in graphical and tabular form for ready use.</p> <p>CONFIDENTIAL</p> <p>Excluded from Automatic Downgrading and Declassification</p> <p>693 02</p> <p>CONFIDENTIAL</p>		

UNCLASSIFIED

UNCLASSIFIED

~~CONFIDENTIAL~~

ATOMICS INTERNATIONAL

A Division of North American Aviation, Inc.

NO. NAA-SR-MEMO-6532

DATE June 26, 1961

PAGE 2 OF 16

INTRODUCTION

Considerable information is available concerning physical and mechanical properties of materials of interest to the SNAP 4 program. The fuel material presently being investigated is Zr-8 w/o U hydride with hydrogen contents of $N_H = 2.8, 3.5, \text{ and } 4.5$. Cladding materials being investigated involve both austenitic (AISI types 304 and 321) and ferritic (AISI type 430) stainless steels.

Properties of interest have been selected from what are considered to be the most reliable sources for both fuel and cladding materials.

I. FUEL MATERIAL PROPERTIES

A. PHYSICAL PROPERTIES

1. Structure and Phase Diagram

The structure of the basic alloy, Zr-8 w/o U is a close packed hexagonal Zr rich solid solution containing precipitated particles of an ordered (epsilon) phase with approximately a composition of Zr_2U . Several phase diagrams of the Zr-H system are available differing only in minor points. Very little information is available concerning the ternary Zr-U-H system in the region of interest. Information was abstracted from a General Atomics report showing ternary isotherms. A partial isopleth was plotted and is shown in Figure 1 with the Zr-H system for comparison. This partial isopleth indicates graphically our lack of knowledge concerning this vital problem.

2. Density

Room temperature density of Zr-8 w/o U is 6.85 gm/cm^3 . A nomograph showing w/o H, H/Zr ratio, H/M ratio, a/o H, N_H , and density of Zr-8 w/o U hydrides is presented as Figure 2.

3. Dissociation Pressure

Pressure-temperature-composition relationships within the Zr-U-H system have been studied by Atkins². Maximum temperatures investigated were approximately 1650°F . Data are sketchy concerning materials in the range of H/Zr 0.8-1.4 in temperature regions where the material is not within the data plus delta phase region. A combination of isochore data from both Atkins and Gilbert³ were used to construct Figure 3.

693 03

UNCLASSIFIED

~~CONFIDENTIAL~~

UNCLASSIFIED

~~CONFIDENTIAL~~

ATOMICS INTERNATIONAL

A Division of North American Aviation, Inc.

NO. NAA-SR-MEMO-6532
DATE June 26, 1961
PAGE 3 OF 164. Electrical Resistivity

Electrical resistivity as a function of temperature is shown in Figure 4 using data from Toy⁴ and GE-ANPD⁵ for Zr-H_x. No data are available for fueled material.

5. Thermal Conductivity

Values for thermal conductivity of zirconium hydride have been extracted from a GE-ANPD⁵ report and are listed in Table I. More recent data reported by DRI⁶ give values as being $12 \pm$ Btu/ft-hr-°F for hydrides containing 45.3 to 56.6 a/o H ($N_H = 3.2-4.7$) in the temperature range 400-1000°F.

TABLE I

THERMAL CONDUCTIVITY OF ZIRCONIUM HYDRIDESTHERMAL CONDUCTIVITY (Btu/ft-hr-°F)

N_H Source Temp. (°F)	0 BMI	2.16 NBS	2.70 BMI	2.89 NBS	3.92 DRI	4.00 BMI	4.10 GE-ANPD	4.89 DRI
70	12.0	--	11.9	--	--	12.1	--	--
200	11.6	--	11.6	9.5	--	11.6	--	--
400	11.1	10.0	11.0	9.4	--	10.8	--	--
600	10.6	10.0	10.7	9.1	--	10.3	--	12.9
800	--	10.0	10.5	9.5	10.4	10.1	10.5	13.1
1000	--	8.4	10.5	9.4	5.8	10.0	--	13.0
1200	--	7.6	--	10.4	7.8	--	--	12.5
1400	--	--	--	--	9.5	--	11.0	13.3
1600	--	--	--	--	10.9	--	--	13.3

Considering the diversity of the values for thermal conductivity it is only safe to say that the thermal conductivity of zirconium hydrides is in the range 11 ± 2 Btu/ft-hr-°F for compositions and temperatures of interest. Thermal conductivity of hydrided Zr-10 w/o U ($N_H \sim 6$) has been studied and reported as 13 ± 1 Btu/ft-hr-°F⁷.

6. Specific Heat

Values for the specific heat of zirconium hydrides have been studied by both the National Bureau of Standards⁸ and BMI⁵. Values are shown in Table II. No values have been reported for fueled hydrides.

UNCLASSIFIED

UNCLASSIFIED

~~CONFIDENTIAL~~~~SECRET~~

ATOMICS INTERNATIONAL

A Division of North American Aviation, Inc.

NO. NAA-SR-MEMO-6532

DATE June 26, 1961

PAGE 4 OF 16

TABLE II

MEAN SPECIFIC HEAT VALUES FOR ZIRCONIUM HYDRIDESSPECIFIC HEAT (Btu/lb-°F)

N _H Source Temp. Range (°F)	0 NBS	1.34 NBS	2.31 NBS	2.70 BMI	2.85 NBS	3.97 NBS	4.00 BMI	4.14 NBS
32- 212	0.0691	0.0738	0.0762	0.076	0.0780	0.0815	0.085	0.0823
212- 392	.0717	.0812	.0880	.088	.0913	.0985	.090	.1006
392- 572	.0772	.0899	.1028	.102	.1078	.1169	.119	.1170
572- 752	.0764	.1013	.1087	.117	.1126	.1261	.136	.1273
932-1022	.0801	.1260	.1402	.139	.1510	.1614	.160	.1808
1067-1112	.0809	.408	.56	.109	.378	.290	.222	.430
1202-1292	.0830	.1096	.1194	.111	.1188	.2176	.222	.2252
1382-1472	.0860	.0909	.1233	.113	.1203	.2100	.222	.2050
1472-1652	--	.0945	.1165	--	.121	.1730	--	.132

7. Thermal Expansion

Thermal expansion values have been determined for a number of fueled hydrides⁹. Curves are shown in Figure 5. Inflection points in the range 470-540°F are probably due to a transformation of a metastable phase. The inflection is lessened by slow heating, slow cooling, and subsequent cycling.

Data from BMI, DRI, and GE-ANPD generally corroborate the results based on their work on unfueled hydrides.

B. MECHANICAL PROPERTIES

1. Ultimate Tensile Strength

Values for tensile strength are difficult to obtain with any degree of reliability due to the high notch sensitivity of the hydrides. BMI performed tests on rod specimens machined after hydriding and tested in a He atmosphere. Figure 6 shows results from this series of tests as reported by GE-ANPD⁵. From the figure, it is evident that above the eutectoid temperature (~1000°F) a considerable reduction of strength occurs which is accompanied by an increase in ductility.

The only reported value for Zr-8 w/o U-1 w/o H is 30,000 psi as given by GA¹⁰.

~~SECRET~~

UNCLASSIFIED

~~CONFIDENTIAL~~

UNCLASSIFIED

NO. NAA-SR-MEMO-6532DATE June 26, 1961PAGE 5 OF 16

ATOMICS INTERNATIONAL

A Division of North American Aviation, Inc.

2. Transverse Rupture Strength

It has been shown that ultimate tensile strength and transverse rupture strength values are the same for brittle materials. Values reported for the transverse rupture strength of hydrides are for the range of H/Zr 0.88-1.5. For Zr at room temperature the strength is $16,000 \pm 4,000$ psi while for Zr-10 w/o U at 500°F the strength is 20,000 psi and at 1000°F the strength is greater than 43,000 psi (the specimen bent).

3. Compressive Strength

For brittle materials the compressive strength is normally considerably greater than values determined in tension. Room temperature values reported for hydrides with H/Zr 0.8-1.0 are a 19,500 psi compressive strength and a 13,000 psi apparent yield strength for zirconium hydride and >142,000 psi compressive strength (specimen bent) and a 119,000 psi apparent yield strength for Zr-10 w/o U hydride. Some evidence of room temperature ductility is shown in these tests.

4. Creep Rupture

A series of creep rupture tests were run at GE-ANPD on hydrided zirconium in a partial pressure of hydrogen. Results are shown in Figure 7. Minimum creep rate data are also available from the same source⁵. A single creep test has been performed at AI on a Zr-8 w/o U alloy hydrided to an H/Zr = 0.74 ($N_H = 2.8$). Under a 6000 psi stress at 1000°F the specimen failed in thirty-three hours with a 93% elongation.

5. Elastic Modulus

Dynamic elastic modulus data on hydrides are shown in Figure 8 based on work performed by Toy⁴. Certain discrepancies are to be noted in his curves. It has been reported^{11, 12} that the addition of uranium to zirconium increases the elastic modulus and also the addition of hydrogen to metal decreases the elastic modulus. Otherwise the slopes of the curves are verified by the other sources.

II. CLADDING MATERIAL PROPERTIES

It was decided to report data from a single source¹³ rather than gather data from a variety of sources. Physical and mechanical properties of AISI type 304, 321, 347, 430 and 446 stainless steels are listed in Table III. Further information is available from various reports in greater detail on some of the properties but is not included for the sake of brevity.

UNCLASSIFIED

NO. NAA-SR-MEMO-6532

DATE June 26, 1961

PAGE 6 OF 16

ATOMICS INTERNATIONAL

A Division of North American Aviation, Inc.

TABLE III

PHYSICAL AND MECHANICAL PROPERTIES OF SELECTED STAINLESS STEELS

	AISI Type Stainless Steel				
	304	321	347	430	446
<u>Composition</u>					
Carbon (%)	<.08	<.08	<.08	<.12	<.12
Chromium (%)	18-20	17-19	17-19	14-18	23-27
Nickel (%)	8-12	9-12	9-13	-	(<.25 N)
<u>Physical Properties</u>					
Density (gm/cm ³)	7.9	7.9	8.0	7.7	7.6
Electrical Resistivity (10 ⁻⁶ ohm-cm)	72	72	73	60	67
Thermal Conductivity (Btu/hr-ft-°F)					
212°F	9.4	9.3	9.3	15.1	12.1
392°F	10.3	10.2	10.2	15.2	12.7
572°F	11.0	11.1	11.1	15.2	13.3
752°F	11.8	11.9	11.9	15.2	13.8
932°F	12.5	12.8	12.8	15.2	14.1
Thermal Expansion Coefficient (10 ⁻⁶ /°F)					
32- 212°F	9.6	9.3	9.3	5.8	5.9
32- 600°F	9.9	9.5	9.5	6.1	-
32-1000°F	10.2	10.3	10.3	6.3	6.3
32-1200°F	10.4	10.7	10.6	-	-
Specific Heat (Btu/lb-°F)					
32-212°F	0.12	0.12	0.12	0.11	0.12

730-V-45 (REV 5-59)

UNCLASSIFIED 693

07

UNCLASSIFIED

NO. NAA-SR-MEMO-6532

DATE June 26, 1961

PAGE 7 OF 16

ATOMICS INTERNATIONAL

A Division of North American Aviation, Inc.

TABLE III - (Continued)

PHYSICAL AND MECHANICAL PROPERTIES OF SELECTED STAINLESS STEELS

	AISI Type Stainless Steel				
	304	321	347	430	446
<u>Mechanical Properties</u>					
Ultimate Tensile Strength (10^3 psi)					
Room Temperature	80	80	80	75	80
600°F	60	--	--	60	72
800°F	55	55	60	55	68
Creep Strength (10^3 psi-10,000 hr Rupture Time)					
800°F	--	--	60	24 (900°F)	--
1000°F	25	33	40	13	--
Elastic Modulus (10^6 psi)					
Room Temperature	28	28	28	29	29

693

08

UNCLASSIFIED

ATOMICS INTERNATIONAL

A Division of North American Aviation, Inc.

UNCLASSIFIED

NO. NAA-SR-MEMO-6532

DATE June 26, 1961

PAGE 8 OF 16

REFERENCES

1. L. D. LaGrange, et al., "A Study of the Zirconium-Hydrogen and Zirconium-Hydrogen-Uranium Systems Between 600 and 800°," J. Phys. Chem., 63 (December, 1959), p 2035
2. D. F. Atkins, "Dissociation Pressures of Hydrided Zirconium-Uranium Alloys," NAA-SR-4245 (AEC Classified Report, February 15, 1960)
3. P. T. Gilbert, Jr., "Zirconium Hydride: 1. Dissociation Pressure," NAA-SR-1399 (AEC Classified Report, April 15, 1956)
4. J. W. Raymond and S. M. Toy, "Mechanical Properties of Hydrides of Zirconium and Zirconium Base Alloys," NAA-SR-Report (To be published)
5. D. S. Parker and C. L. Huffine, "Properties of Hydrided Zirconium," APEX-561 (December, 1959)
6. R. L. Beck, "Research and Development of Metal Hydrides, Summary Report, October 1, 1958 to September 30, 1960," LAR 10 (AEC Classified Report, November, 1960)
7. S. M. Toy and J. B. Vetrano, "Properties of Zirconium Hydride and Zirconium-Uranium Alloy Hydrides," NAA-SR-4244 (AEC Classified Report, February 1, 1960)
8. U. S. Bureau of Standards Progress Report No. 3, October 1, 1956 to December 31, 1956, "Thermal Conductivity and Heat Capacity Projects," (January, 1957)
9. J. D. Watrous, "Thermal Expansion of Hydrided Zirconium Alloys," NAA-SR-6046 (January 27, 1961)
10. U. Merten et al., "The Preparation and Properties of Zirconium-Uranium-Hydrogen Alloys," Proceedings of the International Conference on the Peaceful Uses of Atomic Energy (Geneva, August, 1955), (New York, United Nations, 1956), Vol. 7.
11. W. Chubb and F. A. Rough, "The Mechanical Properties and Heat Treatment Response of Zirconium Uranium Alloys," Trans. Am. Soc. Metals, 51, (1959), p 697
12. J. D. Watrous, "Dynamic Modulus of Elasticity for Zirconium Alloys and Zirconium Alloy Hydrides," NAA-SR-TDR-5755, (October 5, 1960)
13. Metals Handbook, 8th Edition, Vol. 1: Properties and Selection of Materials, (Novelty, Ohio, American Society for Metals, 1961), pp 407-523

UNCLASSIFIED

UNCLASSIFIED

PREPARED BY:

PAGE NO 9 OF 16

CHECKED BY:

NAA-SR-MEMO-

REPORT NO. 6532

DATE:

MODEL NO.

Figure 1. Zr-E Phase Diagram and Zr-S w/o U-H Partial Phase Diagram

UNCLASSIFIED

653-10

UNCLASSIFIED

PREPARED BY:

PAGE NO 10 OF 16

NAA-SR-MEMO-

CHECKED BY:

REPORT NO.

6532

DATE:

 $MW_{92-8} = 95.955 \quad a/o U = 3.22$

MODEL NO

UNCLASSIFIED

653-11

10,000
T(°K)

UNCLASSIFIED

~~SECRET~~

PRESSURE (atm)

Figure 3. Dissociation Pressures for ZrH_x Near Beta-Delta Compositions

~~SECRET~~

UNCLASSIFIED 12

PREPARED BY:

NORTH AMERICAN AVIATION, INC.
UNCLASSIFIED

PAGE NO. 12 OF 16

NAA-SR-MEMO-

REPORT NO. 6532

CHECKED BY:

DATE:

MODEL NO.

Figure 4. Electrical Resistivities of Zirconium Hydrides

UNCLASSIFIED

693

13

UNCLASSIFIED

PREPARED BY:

PAGE NO 13 OF 16

CHECKED BY:

NAA-SR-MEMO-

REPORT NO. 6532

DATE:

MODEL NO.

9.56 8.33

Figure 5. Thermal Expansion of Zr-7 w/o Hydrides

UNCLASSIFIED

653

14

UNCLASSIFIED

NORTH AMERICAN AVIATION, INC.

PREPARED BY:

PAGE NO. 14 OF 16

CHECKED BY:

~~CONFIDENTIAL~~

NAA-SR-MEMO-

REPORT NO. 6532

DATE:

MODEL NO.

Figure 6. Ultimate Tensile Strength of Zirconium Hydrides

UNCLASSIFIED

~~CONFIDENTIAL~~

693

15

UNCLASSIFIED

~~CONFIDENTIAL~~

Figure 7. Creep Strength of Zirconium Hydrides

UNCLASSIFIED

UNCLASSIFIED

NORTH AMERICAN AVIATION, INC.

PREPARED BY:

PAGE NO. 16 OF 16

CHECKED BY:

~~CONFIDENTIAL~~

NAA-SR-MEMO-

REPORT NO. 6532

DATE:

MODEL NO.

Figure 8. Dynamic Elastic Modulus for Zr, Zr-10 w/o U and Their Hydrides

UNCLASSIFIED

~~CONFIDENTIAL~~

693

17