INFORMAL PROGRESS REPORT

MASTER
Contract No. AT(11-1)-3166

ENVIRONMENT AND FRACTURE

Submitted to
Atomic Energy Commission

H. H. Johnson, Professor and Director
Department of Materials Science and Engineering
Cornell University

March 7, 1973

C00-3166-5

NOTICE

This report was prepared as an account of work sponsored by the United States Government. Neither the United States nor the United States Atomic Energy Commission, nor any of their employees, nor any of their contractors, subcontractors, or their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness or usefulness of any information, apparatus, product or process disclosed, or represents that its use would not infringe privately owned rights.

H. H. Johnson, Principal Investigator

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

fy

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency Thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

DISCLAIMER

Portions of this document may be illegible in electronic image products. Images are produced from the best available original document.

INTRODUCTION

The brittleness induced by hydrogen in many structural alloys, particularly at high strength levels, is a prominent and poorly understood problem. It is widely encountered, since hydrogen is a constituent of many natural and industrial environments. In addition, some of the power generation concepts now under study, such as CTR, will require a substantial contact between hydrogen isotopes and structural materials.

The approach to the problem under this contract is on two levels; the first is to improve the characterization of the phenomenology of hydrogen-induced cracking in structural materials, and the second is measurements of the fundamental parameters which are essential to an interpretation of the cracking mechanism. Since hydrogen brittleness is closely related to hydrogen transport through the microstructure, a detailed characterization of the diffusivity and solubility behavior in the brittleness temperature range is essential.

Progress on both levels in 1972-73 is summarized below.

FATIGUE CRACK GROWTH IN STEELS IN HYDROGEN AND HYDROGEN-OXYGEN MIXTURES

The fatigue crack growth characteristics in 4340 steel exposed to hydrogen and hydrogen-oxygen mixtures is strongly dependent upon steel strength level, as described in detail in the accompanying report, Mr. Roger Rowland's M.S. thesis. This was a phenomenological study, designed to improve understanding of the macroscopic parameters which influence hydrogen-induced cracking.

The primary results and conclusions are listed below.

i) Hydrogen accelerates fatigue crack growth in quenched and tempered steels, and fatigue cracks will initiate at lower stress intensities.

ii) The fatigue crack growth behavior in hydrogen is strongly dependent upon strength level in the 150 to 215 ksi range, with the more severe effects encountered at the higher strength level.

iii) There is a pronounced effect of load frequency upon fatigue crack growth rates at the higher strength levels, with faster crack growth rates at the lower frequencies. This is consistent with a model which postulates that hydrogen penetration ahead of the crack tip by diffusion is a precursor to an increment of crack growth. There is little if any measurable effect of load frequency upon fatigue crack growth rates at the lowest strength level. However, the hydrogen still accelerates fatigue crack growth in comparison to an inert environment.

iv) Small oxygen additions to hydrogen completely eliminate the accelerated fatigue crack growth associated with hydrogen at the two lower strength levels, but only partially so at the highest strength level. This demonstrates that the protective influence of oxygen is strength level dependent; it is not known at present if higher oxygen concentrations would provide complete protection at the higher strength level, but the evidence in the literature implies that the answer is no.

v) It is probable that the protective effect of oxygen results from formation of a film which is not permeable to hydrogen; on this interpretation, the strength level must influence the film rupture and re-formation characteristics, presumably because of

an influence of strength level upon the local deformation pattern at the crack tips.

vi) It is clear that oxygen is inert with respect to fatigue crack growth in steel; this is in contrast to the situation with aluminum alloys, where oxygen has been shown to accelerate fatigue crack growth.

vii) The deleterious influence of hydrogen persists to lower strength levels in cyclic loading than static loading.

viii) Approximate calculations suggest that hydrogen may diffuse in advance of the crack tip, perhaps to the distance of the estimated elastic-plastic boundary.

HYDROGEN DIFFUSIVITY AND SOLUBILITY

IN IRON NEAR 300°K

It is suspected that the gradual disappearance of hydrogen brittleness as the temperature is raised above 300°K is most probably due to the thermal release of hydrogen from microstructural traps, a view which implies that hydrogen trapping is an essential step in the brittleness sequence. Further, the strain-rate dependence of hydrogen brittleness suggests that hydrogen transport through the microstructure, perhaps to traps created by deformation, is an essential step.

Further interpretation and quantification of these concepts requires a detailed characterization of hydrogen trapping in iron and steels, and that information is just not available. The experimental difficulty is that the hydrogen solubility near 300°K is very low, essentially not detectable by conventional

techniques.

An initial study of hydrogen trapping in iron was completed during the contrast year 1972-73; this was the Ph.D. thesis of Mr. A. Kumnick, contained in the accompanying report, C00-3166-3. A sensitive permeation technique was used, as described in last year's report and the accompanying thesis. The primary conclusions are

i) Hydrogen trapping is extremely sensitive to the entire detailed thermal and mechanical processing history of the iron. This may be connected with the notorious difficulty in reproducing hydrogen brittleness and stress corrosion behavior in iron and steels.

ii) In the Armco Iron HP studied, two types of traps are induced by deformation; one type (2) is removed by annealing at low temperatures in the recovery range, the second (1) does not appear to be removable by annealing.

iii) Type 2 traps are associated with some feature of the dislocation structure produced by deformation; measurements of the trapped hydrogen concentrations suggests that jogs on dislocations may be the traps. However, this suggestion can only be evaluated from an improved knowledge of the dislocation density and morphology produced by deformation.

iv) In agreement with trapping theory, the permeation flux at steady state is not a function of the microstructure or condition of the material, but is determined solely by the product of the lattice diffusivity and lattice solubility.

v) Puzzling anomalies reported in the literature on a

thickness dependence of the diffusivity in annealed iron are rationalized by the interpretation that all aspects of prior deformation are not removed by annealing, even at very high temperatures. Strong supporting evidence for this view comes from a comparison of permeation results on samples reduced by rolling and chemical thinning prior to annealing. The chemically thinned specimens showed much higher diffusivities after annealing, in agreement with the concept of deformation induced damage that is not removed by annealing.

A considerable effort in the past few months has been devoted to an improved understanding of trapping theory as applied to permeation experiments. From the analysis of McNabb and Foster¹, the trapping equations

$$\frac{\partial C_L}{\partial t} + N \frac{\partial n}{\partial t} = D_L \nabla^2 C_L, \quad (1)$$

D_L = lattice diffusivity

C_L = lattice concentration of diffusing population

N = density of trapping sites

n = fractional occupancy of traps, and

$$\frac{\partial n}{\partial t} = k C_L (1-n) - p n \quad (2)$$

k = transition probability for motion from lattices to trap

p = transition probability for motion from trap to lattice

has an exact solution, under permeation boundary conditions, for

¹A. McNabb and P. K. Foster, Trans. Met. Soc. AIME 227 (1963) 618-627.

the measured permeation time lag of

$$t = \frac{a^2}{D} \left\{ \frac{1}{6} + \frac{\alpha}{2\beta} + \frac{\alpha}{\beta^2} - \frac{\alpha}{\beta^3} (1+\beta) \ln (1+\beta) \right\} . \quad (3)$$

a = jump distance

$\alpha = N k/p$ = trapping parameter

$\beta = C_0 k/p = \frac{n}{1-n}$ = "activity" of trap sites

C_0 = lattice concentration at input surface of the permeation membrane

There are several interesting limiting cases of this equation; it is probable that they can be used to characterize trapping parameters much more accurately than has heretofore been recognized.

i) traps sparingly occupied, $\beta \ll 1$, whereupon the experimentally measured effective diffusivity becomes

$$D_{eff} = D_L (1+\alpha)^{-1}$$

In this limit D_{eff} does not depend upon the lattice input concentration, and hence should be independent of the charging pressure or current density. Further, the same effective diffusivity should be measured by both absorption and evolution techniques.

This effective diffusivity should vary with temperature according to

$$\frac{\partial \ln D_{eff}}{\partial (1/T)} = - \frac{E_m}{k} - \frac{\alpha}{1+\alpha} \frac{E_b}{k}$$

E_m = lattice energy of motion

E_b = binding energy to trap

When the trapping parameter is large, the effective activation

energy will approach the limit

$$E_{\text{eff}} \approx E_m + E_b$$

and for small α

$$E_{\text{eff}} \approx E_m + \alpha E_b$$

ii) traps heavily occupied, $\beta \gg 1$, and the experimental effective diffusivity is now

$$D_{\text{eff}} = D_L \left(1 + \frac{3N}{C_0}\right)^{-1},$$

which is dependent upon C_0 , which in turn is controlled by the charging pressure or current density. A re-analysis of Kumnick's data suggests that this is indeed so, and the relation may be used to estimate the trap density as follows. Rewriting

$$\frac{3N}{C_0} = \frac{D_L}{D_{\text{eff}}} - 1,$$

and when $D_L/D_{\text{eff}} \gg 1$, as it often is, then

$$N = \frac{1}{3} \frac{C_0 D_L}{D_{\text{eff}}} = \frac{1}{3} \frac{J^\infty L}{D_{\text{eff}}}$$

J^∞ = steady state flux

D_{eff} = measured effective diffusivity

Both J^∞ and D_{eff} are measured quantities, and the trap density may be computed from them. A further consequence of the C_0 dependence of D_{eff} is that different effective diffusivities should be measured by absorption and evolution techniques, and this also is apparent in Kumnick's data.

The temperature dependence of the effective diffusivity in

this limit is

$$\frac{\partial \ln D_{\text{eff}}}{\partial (1/T)} = - \frac{E_m}{k} - \frac{3N}{C_0 + 3N} \frac{E_s}{k}$$

E_s = energy of solution of hydrogen in iron

Again, this has two limits, for $3N \gg C_0$

$$E_{\text{eff}} \cong E_m + E_s = E_p$$

E_p = activation energy for permeation

This is a quite remarkable result, since it sets an upper bound for an effective diffusion activation energy associated with trapping, and that upper bound is dependent only on lattice quantities, not on the binding energy for trapping. When $C_0 \gg 3N$

$$E_{\text{eff}} \cong E_m + \frac{3N}{C_0} E_s$$

By appropriate experiments and the use of these various limiting expressions, a very accurate experimental characterization of basic trapping parameters should be feasible.

In more recent experimental work, attention has been directed to the existence of trapping in the annealed iron - studied by Kumnick. It could be most helpful to work with an annealed iron that showed only lattice diffusion, and no trapping. A somewhat higher purity iron has been obtained, with a different melting and processing history, and in preliminary experiments it does not show trapping. This iron will be studied further, and a detailed structural comparison with the iron studied by Kumnick will be undertaken.

DIFFUSION NEAR A MOVING CRACK

The calculations outlined in last year's Progress Report have been completed. From dimensional analysis, the distance of hydrogen penetration ahead of a moving crack should depend on the ratio D/V , where D is the effective diffusivity and V the crack velocity. The exact functional form depends upon the boundary conditions assumed at the crack surface; thus cases of potential physical interest were described in the previous report.

Hydrogen penetration of up to several hundred Angstroms in advance of the crack tip are calculated for reasonable values of diffusivity and crack velocity. The diffusivity is the most difficult parameter to estimate, since the diffusion is occurring in the plastically deforming region ahead of a crack, and substantial trapping effects are present. Nevertheless, significant hydrogen penetration is to be expected.

The boundary conditions, i.e., whether hydrogen enters only at the crack tip or also along the crack flanks, influence the penetration curves mainly at high concentrations near the crack tip. The low concentration region of the concentration profile, which corresponds to the deepest penetration, is quite insensitive to the boundary conditions. This is to be expected, since the hydrogen which penetrates the most no doubt enters right at the crack tip.

GAS PHASE PERMEATION SYSTEM

A prototype gas phase permeation system is now in operation. It was constructed to enable permeation measurements to be made

outside the temperature range in which the electrochemical technique is usable. This is necessary to obtain the lattice permeabilities and solubilities for the iron and steels under study, and also to fully explore the temperature limits of the effective diffusivity described earlier.

The system is also to be used for a study of hydrogen permeation through austenitic stainless steels, if a satisfactory technique for removal of the oxide film can be developed. The present approach is to sputter the oxide film off with krypton ions, and then vapor deposit palladium before the film can re-form. Consistent and reproducible results have not yet been attained. It appears that improved temperature control and recording capability will be necessary.

TIME ALLOCATION

The principal investigator has devoted 20% of his time to the project during the academic year, and will continue to do so for the remainder of the contract year.