Battelle

Pacific Northwest Laboratories
Richland, Washington 99352

AEC Research and Development Report

PACIFIC NORTHWEST LABORATORY
ISOTOPE DEVELOPMENT PROGRAM
QUARTERLY REPORT:
MAY - JULY 1972

AUGUST 1972

NOTICE

This report was prepared as an account of work sponsored by the United States Government. Neither the United States nor the United States Atomic Energy Commission, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately-owned rights.

PACIFIC NORTHWEST LABORATORY

operated by

BATTELLE

for the

U.S. ATOMIC ENERGY COMMISSION

Under Contract AT(45-1)-1830

Printed in the United States of America

Available from

National Technical Information Service

U.S. Department of Commerce

5285 Port Royal Road

Springfield, Virginia 22151

Price: Printed Copy \$3.00; Microfiche \$0.95

3 3679 00061 9686

BNWL-1308-11
UC-23
Radioisotope and
Radiation Applications

PACIFIC NORTHWEST LABORATORY
ISOTOPE DEVELOPMENT PROGRAMS
QUARTERLY REPORT: MAY - JULY 1972

Compiled by J. H. Jarrett

August 1972

BATTELLE
PACIFIC NORTHWEST LABORATORIES
RICHLAND, WASHINGTON 99352

CONTENTS

INTRODUCTION	1
SUMMARY	2
LOW-COST CESIUM AND STRONTIUM SOURCES	5
EVALUATION OF LARGE SCALE USES FOR PURIFIED FISSION PRODUCT XENON	7
STRONTIUM FLUORIDE COMPATIBILITY	9
FISSION PRODUCT RHODIUM, PALLADIUM, RUTHENIUM, AND TECHNETIUM UTILIZATION	11
Technology for Recovery of Rh, Pd, Ru and Tc	11
Economic Analyses of Rh, Pd, Ru and Tc	12
NEUTRON RADIOGRAPHY USING ²⁵² Cf	14
ADVANCED SOURCE DEVELOPMENT	15
CIRCULATORY SUPPORT SYSTEMS	17
Dosimetry Studies	17
Radiological Engineering Studies	17
Miscellaneous	18
NUCLEAR TECHNIQUES FOR SEABED MINERAL EXPLORATION	19
ATLANTIC RICHFIELD HANFORD COMPANY FISSION PRODUCT ACTIVITIES	21

PACIFIC NORTHWEST LABORATORY
ISOTOPE DEVELOPMENT PROGRAMS
QUARTERLY REPORT: MAY - JULY 1972

Compiled by J. H. Jarrett

INTRODUCTION

This report, BNWL-1308-11, is the 23rd report of a series initiated in 1966 to provide detailed and timely information on the results of the isotopic fuels program and related research being conducted at the Pacific Northwest Laboratory by Battelle-Northwest for the U.S. Atomic Energy Commission. The previous reports of the series are BNWL-385, 466, 570, 680, 681, 781, 877, 924, 1010, 1085, 1177, 1256, and 1308-1 through 1308-10.

This report covers the three-month period, May through July 1972.

SUMMARYLOW-COST CESIUM AND STRONTIUM SOURCES

Procedures were developed for fabricating cesium chloride sources by melt casting into a 1 in. $\varnothing$ x 0.035 in. wall x 24 in. long 316 SS capsule. The inner capsule was inserted into a second 316 SS container, 1 1/4 in. $\varnothing$ x 0.035 in. wall x 24 1/4 in. long. Nonradioactive capsules were successfully fabricated. Fission product cesium has been acquired and purified for fabricating two capsules.

EVALUATION OF LARGE SCALE USES FOR PURIFIED PRODUCT XENON

The purification of all stocks of fission product xenon was completed at ORNL. Primary recent interest in this material has been for use in radiation detectors for which a major market could develop for low-cost material.

STRONTIUM FLUORIDE COMPATIBILITY

A preliminary program plan for the SrF_2 compatibility program covering FY-1973 to FY-1974 was prepared and submitted to DAT for review. Selection of containment materials to be evaluated is now underway. Acquisition of the various materials and supplies required for the program is in progress.

FISSION PRODUCT RHODIUM, PALLADIUM, RUTHENIUM, AND TECHNETIUM UTILIZATION

A conceptual process for recovery of Rh, Pd, Ru and Tc from nuclear fuels reprocessing wastes was developed to provide a basis for estimating recovery costs. An analysis to evaluate economic potential of Rh, Pd, Ru and Tc recovery is currently underway. The assumptions and systems diagram have been developed for the model which will be used to estimate recovery and storage costs and revenues.

NEUTRON RADIOGRAPHY USING ^{252}Cf

By cooling the scintillator-film combination used during transfer exposures, an increase in density of over a factor of two can be obtained. A new lens system is being evaluated for use with the image intensifier system for neutron imaging.

ADVANCED SOURCE DEVELOPMENT

The sputtering systems have been thoroughly cleaned and auxiliary systems have been installed to minimize future contamination of the sputtering systems. A handling and storage facility has been fabricated for better radiation control with the AmO_2 target. The laboratory is being modified for better control of extraneous particulate material.

CIRCULATORY SUPPORT SYSTEMS

Parametric computations of dose rates to organ systems and whole body have been initiated, varying the source location.

Final assembly of Phase I heaters is pending receipt of the plutonium-238 heat sources.

Fabrication of the Phase II heater sham has been completed.

Analytical models were developed to estimate temperature distributions in spherical heat sources.

NUCLEAR TECHNIQUES FOR SEABED MINERAL EXPLORATION

Testing of the seabed nuclear probe has been conducted using the 1000 ft cable length. All components have been shown to operate properly. It was necessary to make a few minor modifications including the installation of a voltage rectifier in the underwater pressure housing to provide additional voltage requirements. The underwater testing of the nuclear probe has been delayed due to a leak in the pressure housing of the detector system.

ATLANTIC RICHFIELD HANFORD COMPANY FISSION PRODUCT ACTIVITIES

The Atlantic Richfield Hanford Company (ARHCO) is presently recovering ^{90}Sr and ^{137}Cs for storage. ARHCO is also providing information on production capabilities, product quality, and availability. Strontium as fluoride will be doubly encapsulated in Hastelloy C-276, with 150,000 Ci of ^{90}Sr per capsule.

LOW-COST CESIUM AND STRONTIUM SOURCES

J. A. Partridge, D. H. Siemens, and H. H. Van Tuyl

The objective of this program is to provide technology for the production of inexpensive Cs and Sr sources by using the purified compounds generated in the Hanford Waste Management Program (MWHF). Large scale use of these radioisotopes will require an assessment of the capabilities of MWHF for producing suitable radiation and heat sources, acceptance of the MWHF product by the customer, licensing of the sources, and market development activities.

The goal in FY-1972 is to develop equipment for fabricating smaller diameter sources in the MWHF facility. The incremental cost of producing smaller sources will be evaluated. Prototype sources will be fabricated with nonradioactive feeds, including loading capsules, welding, and NDT. The sources will be tested to determine mechanical integrity. Potential customers will be contacted to stimulate interest in the MWHF sources.

Several melt castings of nonradioactive CsCl were made in 1 in. $\odot$ x 0.035 wall x 24 in. long 316 SS capsules. The first castings were made with the capsules at room temperature. The density of the chloride in the capsules was 2.75 g/cm^3 (69% TD) when the melt was poured slowly and 2.35 g/cm^3 (60% TD) when the melt was poured rapidly. Contraction of the chloride was sufficiently great that the cooled castings could be removed from the capsules without difficulty. Additional castings were made with the capsule heated to $\sim 650^\circ\text{C}$. The capsules were filled to about 3 in. from the top, and then allowed to cool to $\sim 400^\circ\text{C}$. During cooling, a cavity formed down the centerline of the chloride. With the capsule at $\sim 400^\circ\text{C}$, a second pour was made to fill the resulting cavity and the remainder of the capsule. When the capsules were cooled to room temperature, the chloride remained tightly adhered to the inner wall of the capsule. The density of the chloride in these capsules was 2.93 g/cm^3 (75% TD). All castings were made with the CsCl at 700°C in the melter.

One filled capsule was purged with helium and the seal welded closed. The sealed capsule was placed in a test chamber and leak tested with a helium mass spectrometer. No leaks were observed with a leak rate

detection limit of 6.7×10^{-8} atmospheric cm^3/sec . The capsule was then placed in the outer container, (1 1/4 in. OD x 0.035 wall x 24 1/4 in. long 316 SS) purged with helium, seal-welded closed and leak tested in the same manner as the capsule. No leaks were observed in the outer container.

Approximately 60 kCi of ^{137}Cs was received as a partially purified crude from ARHCO. This material was purified in a C-Cell for use in fabricating two prototype sources. Purification was accomplished by absorption on a zeolite ion exchanger, washing to remove sodium, and elution with ammonium carbonate. Because of low equipment capacity, the purification was performed in four batches. The cesium product was concentrated and is being converted to the chloride for source fabrication.

EVALUATION OF LARGE SCALE USES FOR PURIFIED
FISSION PRODUCT XENON

C. A. Rohrmann

Of all the fission products, Xe has the highest fission yield. Although many of the Xe isotopes are radioactive, they all have such short half-lives that their activity would be insignificant after allowing time for normal fuel reprocessing.

In the past, the extreme rarity of Xe in nature has clearly inhibited its consideration for specific large-scale uses even where its properties give it definite and unique advantages. But now, Xe could be made available in surprisingly large quantities. Perhaps the most important and beneficial uses of Xe would be for human surgical anesthesia. Another of the potential uses is as a filler gas in incandescent light bulbs with significant increase in both brightness and efficiency.

The scope of the PNL program is to: (1) establish the quality of Xe which can be accepted or generally licensed for consumer uses, (2) determine what industries would be interested in evaluating fission product Xe for large scale application, (3) distribute specimens to participating evaluators, (4) compile evaluation results, and (5) prepare a final report on the results of this total effort.

Activity in this period has been concerned with interests developing in the field of detectors for low level radiation counters: as a scintillator in place of sodium iodide crystals and as an ionizing medium in a proportional chamber counter. The former is being developed by a group at the Argonne Cancer Research Hospital (University of Chicago) and the latter by a group at the Lawrence Radiation Laboratory (University of California). Both of these groups feel that purified fission product xenon at a price not above \$2.00 per liter would assure an extensive market in these applications. Although the material on hand would need to be purified to a greater degree, such might be done at low cost by one of the suppliers of commercial xenon with whom contacts have been made. Even with this added cost we believe a situation will develop within the nuclear fuel processing industry such that the market price would not exceed the \$2.00 figure. If

yield losses can be minimized, such action may also be taken with the total present available supply of fission product xenon.

Efforts at developing a basis for use in human anesthesia were also continued; however, a definite request for material for this use has not yet been obtained.

The purification of all available crude fission product xenon was completed at ORNL. About nine hundred liters will be available. ORNL has put additional effort on this program in order to achieve a minimum ^{85}Kr content from their system. The goal has been 0.001 μCi of ^{85}Kr per STP liter of xenon. Analytical results have not yet been completed to establish the final level of contamination.

STRONTIUM FLUORIDE COMPATIBILITY

H. T. Fullam

Lower cost strontium is possible by using the Hanford Waste Management Program (HWMP) produced fluoride as a fuel form instead of the currently used titanate. Many potential uses of strontium can be made more cost-effective if the HWMP material can be safely and efficiently utilized. The objective of this program is to determine the chemical compatibility and properties of strontium fluoride as produced by HWP and develop suitable data for strontium fluoride licensing procedures.

The goals in FY-1972 are to establish further contacts with regulatory agencies, detail the program work plan, and initiate the procurement of needed equipment and materials.

The objective of the strontium fluoride compatibility program is to qualify and license the strontium fluoride capsules produced in the Waste Encapsulation and Storage Facilities (WESF) for heat source use under all (or most) anticipated use conditions. It is estimated that the entire program will require approximately five years to complete.

The first two years (FY-1973 and FY-1974) of the program will be divided into three general study areas:

1. Definition of anticipated uses for SrF_2 heat sources; and determination of the data needed to license the sources under use conditions.
2. Characterization of the SrF_2 produced in WESF.
3. Initiation of compatibility testing to determine suitable materials for containing the SrF_2 under the anticipated use and accident conditions.

A preliminary program plan for FY-1973 to FY-1974 was submitted to DAT for review. DAT, in turn, submitted the program plan to compatibility experts at ORNL, BMI, SRL and ML for review and comment. On July 25 a meeting was held at AEC headquarters to discuss the program plan. Present at the meeting were representatives from DAT, DPMM, ORNL, BMI, ML, ARHCO,

and PNL. After a general discussion of the program the representatives from ORNL, BMI and ML were asked to comment on the program plans. It was the opinion of those questioned that the program plan was completely adequate for evaluating SrF_2 compatibility. It was also the opinion that early compatibility testing with high-purity $^{90}\text{SrF}_2$, which was included in our alternate program plan, is highly desirable and that the long-term compatibility test program include an additional time period (6 months).

In a subsequent meeting with DAT it was decided that early testing with $^{90}\text{SrF}_2$ (both high purity and WESF grade) would begin in FY-1973 if additional program funds could be obtained. It was also decided that a six-month test period would be included in the long-term tests.

Work is under way to obtain the supplies and equipment needed for the SrF_2 compatibility program. A laboratory is being set up for the preparation and testing of the nonradioactive test capsules. Preparation and testing of the $^{90}\text{SrF}_2$ capsules will be carried out in the 325 Bldg. hot cells.

Containment materials to be evaluated with SrF_2 will include Hastelloy-C, Haynes 25, TZM, Inconel 625 and additional materials still to be selected. It is anticipated that 8-10 materials will be evaluated in the initial short-term tests. Selection of the additional materials to be tested will be made after a complete review of: SrF_2 source use requirements; previous SrF_2 compatibility work; fluoride corrosion data; thermodynamic considerations and recommendations of recognized experts.

It is anticipated that compatibility testing with high purity SrF_2 will begin in the second quarter of FY-1973. A detailed program plan will be submitted to DAT for review prior to the start of testing.

FISSION PRODUCT RHODIUM, PALLADIUM,
RUTHENIUM, AND TECHNETIUM UTILIZATION

R. P. Roberts and L. L. Clark

The traditional view of fission products as waste materials has been supplanted by their role as a national resource. Pursuant to this revised status, a resource strategy is now being formulated to direct optimum technological and economic application of the fission products Rh, Pd, Ru, and Tc created in operation of nuclear power reactors. This program seeks to evaluate the potential of these artifacts as supplements to the natural reserve of precious metals, and emphasizes the practical aspects of their safe use. The program comprises the following tasks:

1. *Evaluation of Rh and Pd produced in power reactors.*
2. *Technology for recovery of Rh, Pd, Tc, and Ru.*
3. *Market analysis of Rh, Pd, Tc, and Ru.*
4. *Economic analysis of Rh, Pd, Tc, and Ru production from nuclear wastes.*
5. *Fabrication process development for nuclear source (Rh, Pd, Tc, and Ru) products.*

TECHNOLOGY FOR RECOVERY OF Rh, Pd, Ru and Tc

A conceptual process which entails the use of ion-specific or ion-selective ion exchange materials has been developed for the isolation of Rh, Pd, Ru and Tc from high-level acid wastes from nuclear fuels reprocessing. The process has not been demonstrated but has been conceived primarily for the purpose of evaluating the recovery costs of the platinum metals and technetium. In the recovery process it may be highly desirable to separate the Pd and Tc from the Rh and Ru at the same time all four are isolated from the high-level wastes. Rh and Ru require an interim storage prior to utilization to allow for the decay of short half-life isotopes, ^{102}Rh and ^{106}Ru , whereas the Pd and Tc radiation characteristics are not significantly improved by aging. If it is determined advantageous to separate these elements, the conceptual process provides for use of a series of columns each containing the proper ion exchange media.

ECONOMIC ANALYSES OF Rh, Pd, Ru AND Tc RECOVERY

Work was initiated on the task to evaluate the economic factors associated with the recovery of fission products Rh, Pd, Ru and Tc. The factors include the cost of recovery and purification of these elements and the cost of interim storage to allow for the decay of the short-lived radioactive isotopes present in Ru and Rh as well as economic factors associated with marketing of the recovered materials.

The analysis is based on a model consisting of a recovery plant as an adjunct to a 5 MT/d nuclear fuel reprocessing plant. Using this model, a systems diagram was developed to aid in estimating capital equipment costs.

The following assumptions were made for evaluating recovery costs:

Spent reactor fuel is from a PWR of 1970 design with an average exposure of 30,000 MWd/MT.

- The fuels reprocessing plant capacity is 5 MT/d working at 80% of capacity.

The recovery plant capacity is sufficient to process the entire fission product output of the fuels reprocessing plant and would operate on a 3 shift/day, 7 day/week basis.

- Average recovery of the Rh, Pd, Ru, and Tc is 80%.
- Pd and Tc are separated and purified at the time of the initial recovery. Ru and Rh are stored together for 20 years at which time they will be separated and purified.

For the marketing analysis the following assumptions are made:

- All the Pd recovered can be sold immediately.
- A market for Tc will be developed by 1980 and all recovered Tc can be sold at that time.

All Rh and Ru will be salable at the end of the required storage period (20 years for Rh and 25 years for Ru).

- Price projections were increased stepwise every 5 years such that prices in the year 2000 correspond to those predicted by U.S. Bureau of Mines. (1)
- Selling prices of the fission product materials were set at 20% less than those of natural source platinum metals for the period up to 1975. Beyond that period the discount was decreased stepwise because as the supply of platinum metals decreases less price incentive will be required.

From the estimate of the recovery costs and the market analysis, **it** will be possible to make an assessment of the economic potential for the utilization of these fission products.

REFERENCES

- (1) Mineral Facts and Problems, U.S. Bureau of Mines, p. 662 (1970).

NEUTRON RADIOGRAPHY USING ^{252}Cf

K. L. Swinth

The objective of this program is to develop and investigate low-flux neutron radiography techniques and applications using ^{252}Cf . Previous efforts have led to the development of a portable shield and exposure facility for ^{252}Cf thermal neutron radiography. Evaluation of this facility is underway and will lead to recommendations for future designs. Applications of ^{252}Cf neutron radiography will be identified and efforts will be extended to fast neutron radiography.

The major effort in the program is development of techniques for low-flux imaging. A position-sensitive proportional counter is under development that provides for instantaneous readout of data representing the imaged object. Various converter foils, such as Eu and ^6LiF thermoluminescent foils, are being investigated as a means of radiographically recording the images.

A new lens system was designed and tested with the image intensifier using radioactive sources. The lenses have a much larger aperture than the glass lens used previously plus better transmission properties. The image quality is satisfactory and testing with a neutron sensitive scintillator is presently underway.

Cooling of the scintillator-film combination used during transfer exposures provides an increase in density of over a factor of two. The increased density is due to a decrease in the effect of reciprocity law failure with long exposure of the film. When a calcium tungstate intensifying screen is used with Royal Blue* film and a dysprosium transfer foil, a film density of about 1.0 is obtained compared to 2.39 when this combination is cooled to dry-ice temperatures during transfer. Images produced when cooling during transfer show an increase in unsharpness. The reason for the degradation of quality is not known.

* Kodak trade mark.

ADVANCED SOURCE DEVELOPMENT

J. H. Jarrett, W. F. Riemath and G. G. Culver

The objective of this program is to evaluate present and future heat and radiation source application requirements and to relate them to present and future encapsulation technology.

The goal of the current work is concerned primarily with the development of thin-film encapsulation and evaluation techniques for alpha photon sources. Emphasis will be directed toward the technique of sputtering as a means to obtain thin films of radioisotope and containment materials.

The system improvements have continued in this period. Though little experimental work has been completed, the following equipment and room modifications have been accomplished:

Improvements	Benefit
Clean Sputtering Systems; Provide Cold Traps and Related LN ₂ Equipment.	The removal of sputtered material and back-streamed oil should improve pump-down time and minimize chamber contaminants which cause excessive outgassing and could result in poorly adhering films.
Humidity Control System	The installation has been completed and the system is providing lower humidity and constant temperature.
• ²⁴¹ AmO ₂ Target Handling and Storage Facility	A lead handling fixture has been fabricated for the ²⁴¹ AmO ₂ target, which reduces the radiation to a safe level while the operator is installing the target and also provides shielding while the Am target is stored. A dessicator with provisions to evacuate and backfill with inert gas was previously used to store the ²⁴¹ AmO ₂ target.

The experimental work will begin very shortly with emphasis on the preparation of alpha-photon sources using the new $^{241}\text{AmO}_2$ sputtering target and varying the substrates of 304 stainless steel, Inconel 750, and Al_2O_3 . The use of a new mask design and isotope conservation assembly will also be evaluated. Plans are being made for sputtering laboratory modifications that help to control dust and other particulate material in working areas. The purpose of this effort is to minimize loosely adhering foreign particles on radiation source substrates and on radiation sources in preparation, thus leading to better thin film radiation sources.

CIRCULATORY SUPPORT SYSTEMS

F. T. Cross and W. K. Winegardner

The main objective of this program is to determine the dose from radioisotopic heat sources suitable for circulatory support systems. This is accomplished by measuring the dose rates within and surrounding various tissue equivalent phantoms.

Part of the program concerns the prediction of the measured dose rates by the development of computational codes. The computer codes are also used in parametric studies and for the prediction of the in-phantom dose rates from sources not available for measurement.

Another part of the program concerns the development of radioisotopic blood heaters for use in an animal study aimed at assessing the combined effects of heat and radiation in Hanford miniature swine implanted with 50-W plutonium heat sources.

DOSIMETRY STUDIES

The comparison of dose rate measurements and computations continues for the $^{238}\text{PuO}_2^{16}$ Rankine prototypic heat source. Parametric computations of dose rates to organ systems and whole body have been initiated, varying the source location.

RADIOLOGICAL ENGINEERING STUDIESPhase I Heaters

Final assembly of the three blood-cooled heat exchangers will be completed upon receipt of the plutonium-238 heat sources.

Phase II Heaters

Fabrication of the sham that will be used to investigate physical compatibility of the Phase II concept was completed. The Phase II device consists of an isotopic heat source for implantation in the abdomen; a thoracic heat sink or exchanger similar in geometry and application to the Phase I device; and an interconnecting heat conductor. The sham simulates only the size and mass of the heat source and heat conducting cable.

During initial investigations, the approximately 12-in. long cable will be attached to a blood tube (lower insert in Figure 1) interposing the aorta rather than the heat exchanger (upper insert in Figure 1).

MISCELLANEOUS

Analytical models were developed to estimate temperature distributions in spherical heat sources assuming uniform heat dissipation ($0.03 - 0.12 \text{ watts/cm}^2$) directly to surrounding tissue.

FIGURE 1. Sham of Phase II Heater

NUCLEAR TECHNIQUES FOR SEABED MINERAL EXPLORATION

R. W. Perkins, H. G. Rieck, Jr., and N. A. Wogman

In recent PNL studies of the composition of deep ocean sediments, it has been demonstrated that various mineral deposits and commercial-grade ores can readily be identified by neutron activation and instrumental analysis. From preliminary analysis, it is evident that the elemental composition of most mineral deposits can be easily identified at concentrations well below those of economic importance. In-place experience with ^{252}Cf as a neutron source has confirmed these conclusions. Two methods for in-place seabed mineral exploration are being investigated. The first involves placing a neutron source and detector system on the ocean floor. The second method involves bringing the samples on-board ship and employs a shipboard ^{252}Cf irradiator and a Ge(Li) spectrometer. The former technique has the advantage of very rapid analyses, and the latter technique has the advantage that mineral depth profiles can be defined from core sampling. Primary emphasis of the program is presently directed toward the design construction, and the laboratory and sea floor calibration of the in-place seabed nuclear probe.

Testing of the seabed mineral probe revealed problems which were remedied by modification of the hardware system. An electronics package was installed in the pressure housing to provide necessary voltages for proper operation of the preamp and bias voltage supply. A bulkhead connection was installed in the detector pressure housing to provide voltage and signal connection to the 1000 ft cable. A relay switch circuit was installed in the hydraulics pressure housing to provide reversing capability in the hydraulic system.

The irradiator assembly was completed and attached to the system. Adequate manipulators for safe handling of a 260 μg ^{252}Cf source were designed and fabricated. Design of the irradiator assembly provides a seal to prevent seawater from contacting the source during undersea operation. Design also incorporates mechanical restrictions to prevent accidental loss of the ^{252}Cf source during undersea operation.

The detector assembly was tested with the 1000 ft cable and slip ring assembly. Satisfactory performance was achieved. Gamma ray energy spectra were collected in the undersea configuration [pressure housing, lucite and water between detector and large area (source)]. Preliminary results indicate that gamma ray energies through 160 keV will be measurable. Resolution of gamma ray energies by the detector is highly dependent upon the internal pressure (10^{-6} mm Hg or less) in the diode vacuum enclosure. A degradation in resolution resulted when the detector assembly was installed in the probe system. The internal pressure was found to be $\sim 10^{-3}$ mm Hg. The most probable source of the leak is through a faulty "Richards" valve which is used to seal off the diode vacuum enclosure after a pumpdown operation. Replacement of the "Richards" valve is not possible without special environmental chambers. Accordingly, a mechanical attachment is being devised to circumvent the problem.

ATLANTIC RICHFIELD HANFORD COMPANY
FISSION PRODUCT ACTIVITIES

G. E. Benedict and G. L. Borsheim

The Atlantic Richfield Hanford Company (ARHCO) is presently recovering fission products, ^{90}Sr and ^{137}Cs , in the Waste Processing Facility (B Plant) for later encapsulation as SrF_2 and CsCl in the Waste Encapsulation and Storage Facility (WESF). These operations are under contract to the Atomic Energy Commission's (AEC) Division of Production and Materials Management. ARHCO has some engineering effort supported by the Division of Applied Technology (DAT) to provide current and projected information on the ^{90}Sr and ^{137}Cs production capabilities and product quality and availability. ARHCO has liaison responsibilities with Pacific Northwest Laboratory (PNL) and DAT to provide information which will aid possible licensing and commercial use of the $^{90}\text{SrF}_2$ capsules to be produced in WESF.

The $^{90}\text{SrF}_2$ will be doubly encapsulated (0.12 in. x 2) in Hastelloy C-276 with the outer capsule being 20.1 in. in length and 2.625 in. in diameter. The capsule will contain approximately 150,000 Ci of ^{90}Sr . The strontium nitrate solution used for the preparation of SrF_2 in WESF will have to be more pure than the last shipment made to Oak Ridge in order to provide a usable powder for compaction. An additional purification step will separate cations which form insoluble hydroxides at pH 9 to 10.

The annual report for ARHCO activities on DAT programs is in outline form and is scheduled to be issued September 1, 1972.

DISTRIBUTION

No. of
Copies

OFFSITE

2	<u>AEC Albuquerque Operations Office</u>
1	<u>AEC Chicago Patent Group</u> G. H. Lee
10	<u>AEC Division of Applied Technology</u> D. S. Ballantine R. L. Butenhoff D. W. Cole F. D. Haines W. S. Holman J. E. Machurek J. N. Maddox L. A. Miller W. E. Mott R. W. Shivers
1	<u>AEC Division of Biology and Medicine</u> J. D. Goldstein
1	<u>AEC Division of Reactor Development and Technology</u> W. D. Holloman
10	<u>AEC Division of Space Nuclear Systems</u> R. T. Carpenter G. P. Dix D. S. Gabriel M. J. Gaitanis J. S. Griffo N. Goldenberg W. K. Kern A. P. Litman G. A. Newby F. C. Schwenk
1	<u>AEC Dayton Area Office</u> D. D. Davis
2	<u>AEC Oak Ridge Operations Office</u> J. H. Kahn C. Davis, Jr.

No. of
Copies

1	<u>AEC Sandia Area Office</u>
1	<u>AEC Savannah River Operations Office</u> W. D. Sandberg
1	<u>AEC Scientific Representative, England</u>
192	<u>AEC Technical Information Center</u>
1	<u>Aerospace Corporation, Los Angeles (AF)</u>
1	<u>Airesearch Manufacturing Company, Los Angeles</u>
2	<u>Air Force Aeronautical Systems Division</u>
1	<u>Army Reactors Field Group</u>
1	<u>Aro, Inc. (AF)</u>
1	<u>Bellcomm, Incorporated (NASA)</u>
1	<u>Bendix Corporation (NASA)</u>
2	<u>Brookhaven National Laboratory</u> J. Cusack L. G. Stang Jr.
1	<u>Central Intelligence Agency</u>
2	<u>Douglas Aircraft Corporation, MSSD (AF)</u>
1	<u>Dow Chemical Company, Rocky Flats Division (Golden)</u> T. Drouillard
1	<u>du Pont Company, Aiken (AEC)</u> D. H. Turno
1	<u>General Dynamics, Fort Worth (AF)</u>
1	<u>General Electric Company (AEC) (NASA)</u>

No. of
Copies

1	<u>General Electric Company, MSVD, Cincinnati</u>
M. Bromberg
1	<u>General Electric Company, MSVD, Valley Forge</u>
P. E. Brown
1	<u>General Electric Company, Vallecitos Laboratory</u>
J. F. Jaklevick
1	<u>Grumman Aircraft Engineering Corporation (NASA)</u>
2	<u>Hughes Aircraft Company, Aerospace Group,</u>
<u>Culver City, California</u>
F. N. Magee
K. W. Cowans
1	<u>Los Alamos Scientific Laboratory</u>
<u>University of California</u>
<u>Los Alamos, New Mexico</u>
H. A. O'Brien, Jr.
1	<u>Massachusetts Institute of Technology, (Rasmussen) (AEC)</u>
1	<u>Massachusetts Institute of Technology, (Lexington) (AF)</u>
2	<u>Mound Laboratory (AEC)</u>
W. T. Cave
R. K. Flitcraft
1	<u>NASA Ames Research Center</u>
4	<u>NASA Goddard Space Flight Center</u>
W. C. Isley (1)
1	<u>NASA Langley Research Center</u>
1	<u>NASA Lewis Research Center, Cleveland</u>
Lloyd Shure
2	<u>NASA Manned Spacecraft Center</u>
Tony E. Redding (1)
1	<u>NASA Marshall Space Flight Center</u>

No. of
Copies

2	<u>NASA, Washington</u>
4	<u>National Reactor Testing Station</u> Aerojet Nuclear Company P.O. Box 1845 Idaho Falls, Idaho R. J. Gehrke
1	<u>Navy, Nuclear Power Division (Washington)</u> Graham Haigie (NAVFAC)
1	<u>Navy Air Systems Command</u>
1	<u>Navy Facilities Engineering Command</u> Bureau of Yards and Docks Annex Washington, D.C. 20390 L. Derderian
1	<u>Navy Office of the Chief of Naval Operations</u>
3	<u>Navy Ordnance Systems Command</u>
1	<u>Navy Ship Systems Command Headquarters</u>
1	<u>Navy Space Systems Activity</u>
1	<u>Nuclear Materials and Equipment Corporation (AEC)</u> C. S. Caldwell
2	<u>Oak Ridge National Laboratory (AEC)</u> J. H. Gillette A. F. Rupp
1	<u>Radio Corporation of America (AEC)</u>
1	<u>Rand Corporation (AF)</u>
1	<u>Savannah River Laboratory</u> Aiken, South Carolina D. H. Turno
1	<u>Sanders Nuclear Corp., Nashua, N.H.</u> Douglas Harvey

No. of
Copies

- 1 TRW Space Technology Labs, Redondo Beach, California
W. M. Bowes
- 1 Westinghouse Electric Corporation, Lima (NASA)
- 1 Wright-Patterson AFB, Dayton, Ohio
Capt. D. C. De Pree

ONSITE

- 1 AEC Chicago Patent Group
R. M. Poteat
- 2 AEC Richland Operations Office
W. E. Lotz
Attn: B. J. Melton
H. A. House
- 8 Atlantic Richfield Hanford Company
G. L. Borsheim
H. H. Hopkins
G. A. Nichleson
G. C. Oberg
A. E. Smith
P. W. Smith
M. J. Szulinski
ARCO Files
- 3 Donald W. Douglas Laboratories
M. Lewis
W. E. Matheson
Files
- 1 Douglas United Nuclear
J. W. Riches
- 38 Battelle-Northwest
E. M. Alpen
J. M. Batch
T. D. Chikalla
F. T. Cross
G. J. Dau
D. C. Deonigi
K. Drumheller
P. L. Farnsworth

No. of
Copies

Battelle-Northwest (Continued)

J. W. Finnigan	A. M. Platt
H. T. Fullam	F. P. Roberts
J. E. Hansen	C. A. Rohrmann
A. J. Haverfield	J. R. Sletager
J. H. Jarrett (4)	K. L. Swinth
R. S. Kemper	H. H. Van Tuyl
R. W. McKee	J. B. Vetrano
E. T. Merrill	E. J. Wheelwright
J. E. Minor	N. A. Wogman
J. M. Nielsen	Technical Information Files (5)
R. E. Nightingale	Technical Publications
R. W. Perkins	