Report No. BMI-1340
UC-25 Metallurgy and Ceramics
(TID-4500, 14th Ed.)

Contract No. W-7405-eng-92

PROGRESS RELATING TO CIVILIAN APPLICATIONS
DURING APRIL, 1959

by

Russell W. Dayton
Clyde R. Tipton, Jr.

May 1, 1959

BATTELLE MEMORIAL INSTITUTE
505 King Avenue
Columbus 1, Ohio

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency Thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

DISCLAIMER

Portions of this document may be illegible in electronic image products. Images are produced from the best available original document.

TABLE OF CONTENTS

	<u>Page</u>
REPORTS RELATING TO CIVILIAN APPLICATIONS ISSUED DURING APRIL, 1959	5
A. ASSISTANCE TO HAPO	7
Thermal Conductivity of Uranium and UO_2	7
Mechanical Properties of Zirconium Alloys	8
Preparation of Molybdenum Single Crystals	8
Physical Distortion of Graphite	9
Evaluation of Possible Loss-of-Coolant Incidents in the Plutonium Recycle Test Reactor	10
End-Capping Methods for Coextruded Fuel Pins	11
A Photographic Study of the Corrosion of Defected Fuel Elements in High-Temperature Water	11
B. DEVELOPMENTS FOR ALUMINUM-CLAD FUEL ELEMENTS	13
Preparation of Aluminum-Uranium Alloys	13
C. RADIOISOTOPE AND RADIATION APPLICATIONS	15
Development of Radioactive-Tracer Quality-Control Systems	15
Use of Intrinsic Radioactive Tracers for Process Control	16
Radiation Chemistry of Inclusion Compounds	17
Graft-Polymerization Studies	18
Nitration of Hydrocarbons	19
D. PROCESSING OF FEED MATERIALS	21
Solidification of Uranium	21
E. SPRAY DEPOSITION OF CALCIUM METAL ON NICKEL OR INCONEL	23
F. RESEARCH FOR AEC REACTOR DEVELOPMENT DIVISION PROGRAM	25
REACTOR MATERIALS AND COMPONENTS	25
Valence Effects of Oxide Additions to Uranium Dioxide	26
High-Pressure High-Temperature Solid-State Studies	28
Fueled Zirconium Hydride Moderator	29
Irradiation Surveillance Program on Type 347 Stainless Steel	29
Development of Niobium-Base Alloys	33
Development of Corrosion-Resistant Niobium Alloys	33
Rubbing Surfaces in Sodium Environments	38
STUDIES OF ALLOY FUELS	40
Development of Niobium-Uranium Alloys	40
Development of Thorium-Uranium Alloys	42
FISSION-GAS RELEASE FROM REFRACTORY FUELS	47
GENERAL FUEL-ELEMENT DEVELOPMENT	50
Fabrication of Cermet Fuel Elements	50
Gas-Pressure Bonding of Molybdenum- and Niobium-Clad Fuel Elements	52
The Irradiation of UC- and UN-Stainless Steel Dispersion-Type Fuel Elements	54
Factors Affecting Pressure Bonding	54
FF. FUEL-CYCLE PROGRAM STUDIES	57
GAS-PRESSURE BONDING OF CERAMIC, CERMET, AND DISPERSION FUEL ELEMENTS	57
DEVELOPMENT OF URANIUM CARBIDE-TYPE FUEL MATERIALS	58
Fabrication of UC by Powder Processes	59
Physical Characteristics and Properties of Uranium Carbides	60
Uranium Monocarbide Diffusion Studies	60
G. FATIGUE STUDIES OF INCONEL AND INOR-8	63
Fatigue Studies of Inconel	63
Fatigue Studies of INOR-8	63

TABLE OF CONTENTS
(Continued)

	<u>Page</u>
H. PHYSICAL RESEARCH	65
Niobium-Gas Reactions	65
Constitution of Uranium-Niobium Alloys	66
I. SOLID HOMOGENEOUS FUELED REACTORS	69
Fission-Product Release During Postirradiation Heating of Uranium Oxide/Carbide- Graphite Spheres	69
Fission-Product Release During Irradiation of Uranium Oxide/Carbide-Graphite Spheres	72
J. PROBLEMS ASSOCIATED WITH THE RECOVERY OF SPENT REACTOR FUEL ELEMENTS	73
CORROSION STUDIES	73
The Darex Process	73
The Sulfex-Thorex Process	74
The Darex-Thorex Process	74
The Zirflex Process	75
The Fluoride-Volatility Process	75
STUDY OF THE EFFECT OF IRRADIATION ON CLADDING- AND CORE-DISSOLUTION PROCESSES	76
K. DEVELOPMENTS FOR SRE, OMRE, AND OMR	79
EVALUATION OF URANIUM MONOCARBIDE AS A REACTOR FUEL	79
Irradiation of Uranium Monocarbide	79
Postirradiation Examination of Uranium Monocarbide	80
Preparation of UC Pins for Irradiation in the SRE	80
L. TANTALUM AND TANTALUM-ALLOY STUDIES	81
Development of Container Materials for LAMPRE Applications	81
Effect of Irradiation on Tantalum	85
M. DEVELOPMENTAL STUDIES FOR THE PWR	87
Pressure Bonding of Zircaloy-2-Clad Fuel Elements Containing Compartmented Oxide Fuel Plates	87
N. DEVELOPMENT FOR THE MGCR	91
FABRICATION AND IRRADIATION OF FUEL MATERIALS	91
Fabrication of BeO-UO ₂ Fuel Elements	91
Fabrication of Graphite Fuel Elements	91
Development of BeO-Clad UO ₂ Pellets	92
Radiation-Effects Study of Potential Fuels	92
CORE-MATERIALS IRRADIATION PROGRAM	93
O. ENGINEERING ASSISTANCE TO KAISER ENGINEERS	95
Reactor Flow Studies	95
P. DEVELOPMENTAL STUDIES FOR THE SM-2	97
Development of Fuel Materials	97
Encapsulation Studies	101
Q. GAS-COOLED REACTOR PROGRAM	103
MATERIALS DEVELOPMENT PROGRAM	103
Effects of Irradiation	103
Encapsulation Studies	104
Fabrication of UO ₂ Pellets	105
IN-PILE-LOOP PROGRAM	107
BRR Loop Program	109
ETR Loop Program	109

REPORTS RELATING TO CIVILIAN APPLICATIONS
ISSUED DURING APRIL, 1959

- BMI-1328 "Application of Ultrahigh-Pressure High-Temperature Equipment to Study of UO_2 Reactions", by Wendell B. Wilson.
- BMI-1329 "Solubility of Lithium Hydroxide in Water and Vapor Pressure of Solutions of Lithium Hydroxide Above 220F", by Elmer F. Stephan and Paul D. Miller.
- BMI-1330 "Progress Relating to Civilian Applications During March, 1959", by Russell W. Dayton and Clyde R. Tipton, Jr.
- BMI-1332 "Reactions in the Niobium-Hydrogen System", by William M. Albrecht, W. Douglas Goode, Jr., and Manley W. Mallett.

A-1

A. ASSISTANCE TO HAPO

F. R. Shober

Measurements of the thermal conductivity of irradiated uranium and UO_2 have been delayed. Modification of the equipment is complete but fitting of auxiliary apparatus is necessary. In the study of the mechanical properties of zirconium alloys, five creep tests on 15 per cent cold worked Zircaloy-2 have been discontinued after approximately 13,000 hr. Three cyclic-temperature tests were discontinued after 3,000 hr. Work continues on the preparation of molybdenum single crystals. Attempts to grow additional single crystals have been unsuccessful and plans are being made to determine if variations in purity or fabrication history are responsible for the inconsistent results.

Sink-float density measurements, a technique being used to identify and study factors affecting irradiation-induced volume changes in graphite, are continuing. Efforts have been continued to improve the reproducibility of the experimental method. Satisfactory reproducibility was obtained by making repeated separations of a given sample at a given liquid density. A digital computer is being used to simulate conditions after a loss-of-coolant incident in the Plutonium Recycle Test Reactor (PRTR). The cases to be evaluated include the rupture and displacement of a 14-in. outlet pipe, a single 14-in. hole, and ruptures of one of the 1-1/2-in. jumpers attached to each process tube. Calculations for one case have been completed. In the study of end-capping methods for coextruded fuel pins, preparations are being made to evaluate several different joint designs and joining techniques. A photographic record of the action of high-temperature water on defected Zircaloy-2-clad uranium fuel specimens will be obtained in a new program started this month.

Thermal Conductivity of Uranium and UO_2

C. F. Lucks and H. W. Deem

Uranium

The irradiated natural uranium specimens have been examined and measured. The specimens are sound and can be used for thermal-conductivity measurements. Preparations for making thermal-conductivity measurements on the irradiated uranium specimens are proceeding concurrently with those for the UO_2 measurements.

Uranium Oxide

Modification of the apparatus for hot-cell use has been completed except for some fitting of the auxiliary equipment. The apparatus will be moved to the hot cell, and thermal-conductivity measurements will be started. During April, the second set of irradiated UO_2 specimens was received.

Mechanical Properties of Zirconium Alloys

F. R. Shober and J. A. VanECHO

The utilization of 15 per cent cold-worked Zircaloy-2 as material for process tubes for the NPR has indicated the need for study of the creep properties at elevated temperatures. Tests at 290, 345, and 400 C are being run on cold-worked and annealed material. Cyclic-temperature tests, 6 days at temperature (290 or 345 C) and 1 day at room temperature, are being run at stress levels comparable to tests run under constant-temperature conditions. Tests on annealed Zircaloy-2 specimens have been continued at 290, 345, and 400 C to compare their long-time creep properties with 15 per cent cold-worked and annealed material from another heat.

Twenty vacuum-creep machines are being used for this program. Five of the long-time creep tests were discontinued during this work period after approximately 13,000 hr at test. Three were at 290 C and 30,000, 25,000 and 20,000 psi, respectively, and two were at 345 C and 20,000 and 15,000 psi. Total deformation after 12,500 hr for the two higher stresses at each temperature was approximately 0.55 per cent. The minimum creep rates obtained from the five tests were <0.00001 per cent per hr. A comparison of total deformation at 12,500 hr for the two tests at 20,000 psi showed that an increase in temperature from 290 to 345 C had increased total deformation by approximately a factor of two.

Three cyclic-temperature tests were discontinued after 3000 hr at temperature. The results after test indicate that cyclic test temperature produces slightly more total deformation than constant test temperature.

Additional tests on the annealed Zircaloy-2 will be started in those creep units that have been vacated by discontinuing the above tests.

Preparation of Molybdenum Single Crystals

J. A. DeMastry, F. R. Shober, and R. F. Dickerson

Single crystals of high-purity molybdenum are being grown in a modified Andrade furnace. Use is made of a steep temperature gradient along the length of the specimen to obtain growth of a single crystal. This temperature gradient is obtained by resistance heating the molybdenum rod and water cooling the ends of the rod. Six single crystals of high-purity molybdenum have been grown in 1/8-in.-diameter rod at a current of 240 amp at approximately 3.0 v for 5 to 6 hr. Since all rods of molybdenum do not produce single crystals, it has been postulated that either the purity or the fabrication history of the molybdenum rods influences the growth of single crystals. Spectrographic analysis will be made of the material from the various lots. Several unsuccessful runs have been made. Additional molybdenum rod has been received, but no attempts to grow single crystals from this material have been made as yet. One or two specimens are to be elongated 1 to 2 per cent in a tensile machine prior to annealing in an attempt to use a modified strain-anneal technique.

A-3

Physical Distortion of Graphite

J. Koretzky, W. C. Riley, and W. H. Duckworth

Research to identify factors affecting irradiation-induced volume changes in graphite by means of sink-float density measurements was continued. An effort was made to refine the density-distribution curve by increasing the number of densities at which separations were made. Poor reproducibility of data resulted from entrapment of a significant percentage of float by the sink material.

During this month, efforts were continued to improve the reproducibility of the experimental method. Satisfactory reproducibility was obtained by making repeated separations of a given sample at a given liquid density. After each separation the sink material was forced into suspension. When no float appeared after centrifugation the specific gravity of the benzene-bromoform solution was increased and the procedure was repeated. The density distributions of two samples of minus 40 plus 60-mesh TS-GBF graphite from Bar 127-86 were measured. The results are in close agreement and are summarized in Table A-1.

TABLE A-1. DENSITY DISTRIBUTION OF MINUS 40 PLUS 60-MESH TS-GBF GRAPHITE (FROM BAR 127-86)

Sample 1			Sample 2		
Specific Gravity of Benzene-Bromoform Solution	Amount Floated, w/o	Cumulative Amount Floated, w/o	Specific Gravity of Benzene-Bromoform Solution	Amount Floated, w/o	Cumulative Amount Floated, w/o
1.850	0.10	0.10	1.850	0.10	0.10
1.903	0.08	0.18	1.905	0.08	0.18
1.943	0.14	0.32	1.947	0.12	0.30
1.991	0.28	0.60	1.991	0.28	0.58
2.046	1.54	2.14	2.046	1.35	1.93
2.097	9.34	11.48	2.097	9.21	11.14
2.150	47.74	59.22	2.150	48.10	59.24
2.193	35.13	94.35	2.189	34.53	93.77
2.267	5.65	100.00	2.268	6.23	100.00

Samples of TS-GBF were sized to minus 40 plus 140-, minus 140 plus 270-, and minus 325-mesh and sent to HAPO for irradiation.

The density distributions of several samples of minus 325 TS-GBF graphite will be measured and compared. Further measurements on an irradiated sample, N19-232, will be made.

Evaluation of Possible Loss-of-Coolant Incidents
in the Plutonium Recycle Test Reactor

C. A. Alexander, L. E. Hulbert, A. W. Lemmon, Jr.,
and R. B. Filbert, Jr.

The simulation of conditions after a loss-of-coolant incident in the PRTR by means of a digital computer was continued this month. Four postulated incidents are being considered. Case I, that of a rupture and displacement of a 14-in. outlet pipe, has been simulated and the fuel-element temperatures have been computed as a function of time. The computation was divided into four phases: (1) the blowdown phase where a water-steam mixture would be flowing through the process tubes, (2) a steam-flow phase where steam generated in the bottom ring header would flow through the process tubes and out the rupture, (3) an adiabatic phase where the reactor would be filled with stagnant steam, and (4) an injection phase where emergency backup coolant would be added to the bottom ring header.

Computation of the blowdown and steam-flow phases for this postulated incident indicate that cooling would occur in both phases and a hottest point temperature for a six-rod element would be 540 F at 26 sec after the incident.

The calculation of the adiabatic phase was continued until the melting point of the cladding material was reached at about 16 min after the incident.

The proposed injection system would allow emergency backup light-water coolant to enter the ring headers at a rate of 375 gpm when the system pressure falls below the pump pressure of 100 psi. This situation would occur at 24 sec after the incident, and at 84 sec after the incident the injection water would reach the bottom of the fuel elements. The machine computation indicated that at 108 sec after the incident the fuel elements would be covered with water and that no melting would occur. At this time the injection rate could be substantially reduced.

Injection water reaching the bottom of the elements 10 and 15 min after the incident also would be sufficient to prevent melting, although the 15-min injection time would result in substantial reaction between the Zircaloy cladding and the water.

Case II, that of a single 14-in. hole, was found to present no serious hazard with the present injection system.

During the next month, Cases III and IV will be studied. These cases deal with ruptures of one of the 1-1/2-in. jumpers attached to each process tube. A preliminary analysis indicates that the intact process tubes may present the more critical situation, hence both the "victim" process tube and an intact tube will be employed in the analysis. It is further planned to extend the analysis which has been made for the 19-rod cluster UO₂ element for Case I to the cluster plutonium-aluminum element and the Mark II-B concentric-ring UO₂ element.

A-5 and A-6

End-Capping Methods for Coextruded Fuel Pins

R. M. Evans, J. J. Vagi, and R. L. Koppenhofer

A survey of end-capping methods for coextruded fuel pins is being made for Hanford Atomic Power Operations. Work has been continued on the literature survey on end capping. Several promising joint designs and joining techniques have been chosen for study in the laboratory. Specimens, dies, fixtures, and other necessary hardware for use in laboratory studies are being prepared. Laboratory tests are scheduled to begin in May.

A Photographic Study of the Corrosion of Defected Fuel Elements
in High-Temperature Water

E. F. Stephan and F. W. Fink

A photographic record is desired of the action of high-temperature water on defected fuel elements. Time-lapse color motion pictures are to be taken of corroding specimens through a windowed autoclave.

The equipment is being assembled. Preliminary calibration tests will be started in May.

B-1 and B-2

B. DEVELOPMENTS FOR ALUMINUM-CLAD FUEL ELEMENTS

Preparation of Aluminum-Uranium Alloys

N. E. Daniel, E. L. Foster, and R. F. Dickerson

Aluminum-uranium alloys containing greater than 20 w/o uranium are desired in the form of hollow cylindrical extrusion billets for subsequent fabrication into tubular fuel elements. The contemplated fabrication technique, coextrusion with aluminum to form a fuel element clad inside and outside with aluminum, makes it necessary that the cast shapes be sound and relatively homogeneous. A program of research concerned with investigation of centrifugal casting of the aluminum-35 w/o uranium alloy as a more satisfactory method of producing good-quality extrusion billets is being concluded. Previous work has shown that small quantities of a third element when added to binary aluminum-uranium alloys will improve their fabricability and may make the 35 w/o uranium alloy more compatible with aluminum for coextrusion. Therefore, the effects of selected additions on the castability and fabricability of binary aluminum-35 w/o uranium alloy have also been investigated.

Final evaluation of the 26-in. -long aluminum-35 w/o uranium extrusion billets has been held in abeyance pending the receipt of chemical analyses of samples taken along the length of the casting. These analyses are required to evaluate the material balance and to aid in interpreting the results of metallographic and radiographic examinations.

Because the tensile data obtained on the as-cast material have indicated a definite improvement in the tensile properties of the alloys containing 3 w/o silicon, tin, and zirconium, further tensile tests of these alloys in the extruded condition will be made. The data obtained from these tests should indicate the effects of structure on the tensile properties of the alloys.

Except as noted above future work will be confined to the compilation and correlation of the data obtained to date.

C-1

C. RADIOISOTOPE AND RADIATION APPLICATIONS

P. Schall

Programs on the use of tracers for cement quality control, use of intrinsic tracers for process control, radiation chemistry of inclusion compounds, and radiation-induced graft polymerizations were continued and a new program on radiation-induced nitration reactions was initiated during the month.

In the development of tracer quality-control techniques for cement the major effort was applied to the definition of the concentration range for which the radiometric titration for magnesium may be accomplished with good accuracy, the application of activation analysis to cement, and the refinement of the EDTA titration for calcium analysis using a radiometric endpoint.

As a result of the survey and evaluation of various processes several have been selected for laboratory evaluation and development of techniques for process control using intrinsic tracers.

All planned irradiations of inclusion compounds have been completed. During the remainder of the program the effort will be devoted to detailed analysis and evaluation of the chemical products formed.

The effort on radiation-induced graft polymerization was devoted to continued study of factors influencing the formation of grafting sites. Results are reported on free-radical storage in polymethyl- and polyoctylmethacrylate and on peroxy-site formation in polymethylmethacrylate.

Design of the irradiation apparatus for the nitration-reaction studies has been completed. Ambient-temperature irradiations of nitric acid-cyclohexane are being made to provide material for establishing suitable product-analysis techniques.

Development of Radioactive-Tracer
Quality-Control Systems

T. S. Elleman, C. T. Brown, D. N. Sunderman,
and M. Pobereskin

The study of the radiometric analysis of magnesium has been resumed. Analyses were made of solutions containing approximately 25 mg per 100 ml of MgO. The results of these runs are summarized in Table C-1.

C-2

TABLE C-1. PRECISION OF RADIOMETRIC MAGNESIUM ANALYSIS

MgO Concentration, mg per 100 ml		Experimental Average	Standard Deviation	Absolute Error, per cent
Theoretical	Experimental			
24.25	24.51	24.42	±0.109	0.70
	24.55			
	24.32			
	24.31			

The precision and accuracy of the method at this concentration are well within 1 per cent, but the results are all higher than expected. The absolute error of 0.70 per cent may be compared with 0.21 per cent for 10 mg per 100 ml of MgO and no error for 5 mg per 100 ml of MgO. A concentration range of 5 to 15 mg per 100 ml of MgO is recommended for this analytical method.

Neutron-activation analysis has been performed on various standard samples to check the analytical technique. Experiments were conducted to check the geometry of the detector and the dead time of the 100-channel analyzer. In addition, it was desired to obtain good gamma spectra from high-purity silica and to ascertain if magnesium could be determined in the presence of manganese. Correction for dead time and geometry did not compare closely with prediction due to incorrect function of the amplifier in the 100-channel analyzer. Good gamma spectra on irradiated SiO₂ were obtained, however. It was also ascertained that the 0.85-Mev gamma peak of manganese-56 interferes with both the 0.84- and 1.02-Mev gamma peaks of magnesium-27 to such an extent that it is impossible to detect the presence of magnesium when present in a thirtyfold excess concentration.

Work is continuing on the calcium analysis in order to improve the precision of the method. Results obtained during this report period indicate that a precisely buffered solution is necessary for consistent analyses.

Work during the next report period will include a reinvestigation of the activation analysis of cement standards, and activation analyses of cement raw materials. Investigation of the radiometric calcium analysis will be concluded, and the effect of interfering elements on the radiometric method for magnesium will be determined.

Use of Intrinsic Radioactive Tracers for Process Control

J. L. McFarling, D. N. Sunderman, and M. Pobereskin

A summary of the results of the preliminary phase of this investigation, selection of processes for more detailed study, was discussed in mid-April with personnel of the Office of Isotopes Development. At this meeting the decision was made to begin the more detailed study of a limited number of process applications.

Radiotracer control applications tentatively chosen as typical examples for further study were the following:

C-3

- (1) Use of radiocopper to control the separation of copper from nickel in the ammonia-leach nickel-refining process
- (2) Use of a suitable tracer such as sodium-24 to control thickness and uniformity of glaze on ceramic tile, or adhesive on corrugated paperboard
- (3) Use of radiosodium to control chemical-recovery processes in sulfate pulping
- (4) Use of radiosilver as a means of quality control in manufacturing phosphors.

The ensuing phase of this program is proceeding along two lines of endeavor. Laboratory experiments are being conducted for the purpose of defining the sensitivity and accuracy of the proposed radiotracer control techniques. In conjunction with the experimental work on a given process application, contacts will be made with representatives of some industry using the process in order to get their viewpoint, and promote industrial cooperation throughout the remainder of the program.

In May, bench-scale experiments relating to the copper-removal step in the ammonia-leach nickel-refining process will begin. The Canadian firm Sherritt-Gordon Mines, Ltd., of Ft. Saskatchewan, Alberta, will be the industrial processor contacted in this case.

As the time schedule permits, the other processes listed above will be evaluated in a manner similar to that outlined for the copper-removal process.

Radiation Chemistry of Inclusion Compounds

M. J. Oestmann, M. J. Landon, E. J. Kahler,
and W. S. Diethorn

During the month of April the last series of irradiations in the cobalt-60 facility was completed. No additional irradiations are planned in the program. Chemical analysis of the irradiated complexes is continuing.

All the effort in the analytical phase of the program this month was devoted to the chemical analysis of the urea-dodecane complex. Infrared and gas-chromatography analyses of the hydrocarbon phase separated from this complex showed the presence of low-molecular-weight paraffins and olefins, and compounds containing oxygen and nitrogen. In earlier phases of the program there was good evidence that these latter compounds were amides. An attempt was made to characterize these compounds in more detail. An aliquot of the hydrocarbon phase was reacted with thionyl chloride to convert the amides to the more volatile nitriles to facilitate gas chromatographic analysis.

Evidence for the presence of a 12-carbon nitrile, corresponding to the amide of dodecane, was obtained. Infrared analysis supports the presence of this nitrile. No

C-4

homologous series of nitriles was found. However, the products from the thionyl chloride reaction are complex and there is evidence of the presence of nitrogen-containing compounds other than amide. These compounds have not been identified.

In a further attempt to characterize the amide an aliquot of the hydrocarbon phase separated from the dodecane-urea complex was vacuum distilled. The volatile fraction contained only paraffins and olefins. Infrared spectra of the distillation residue showed evidence of an amide but other compounds in the residue have not been identified. Gas chromatography of the distillation residue and its thionyl chloride reaction product revealed a number of compounds which have not been characterized.

The current work with the dodecane-urea complex suggests that, in addition to amide, other nitrogen-containing compounds are produced during irradiation. Compounds that may be present include the aliphatic ureas, biureas, and biurets.

Further analysis of the dodecane-urea complex will be the chief effort in May. Analysis of the octane-urea complex will be postponed until better analytical techniques for the dodecane complex can be worked out. Results from the analysis of the irradiated nickel cyanide complex of benzene will be available next month.

Graft-Polymerization Studies

I. S. Ungar, J. F. Kircher, R. A. Markle,
and R. I. Leininger

The program on radiation-induced graft polymerization is continuing with emphasis on the investigation of factors influencing the formation of free-radical and peroxy grafting sites.

Last month a maximum free-radical concentration of seven per polymer molecule was reported for polymethylmethacrylate irradiated at dry-ice temperatures for 2 hr at a dose rate of 3.5×10^5 rads per hr. This corresponds to a free-radical concentration of 7×10^{-3} per monomer unit. Lowering the temperature to -195.8°C under the same radiation conditions yielded no increase in free-radical concentration.

Polymethylmethacrylate was grafted with vinylpyrrolidone under conditions which produced approximately five free-radical sites per polymer molecule. Nitrogen analyses of the samples fractionated on the basis of solubility in acetone-methanol mixtures indicated that grafting occurred. The maximum graft chain length was 66 vinylpyrrolidone units. An additional experiment with a 50-50 vinylpyrrolidone-benzene solution showed that the length of the graft chain may be controlled by varying the monomer concentration. In this latter case, the chain was approximately 50 monomer units long.

A sample of polyoctylmethacrylate with a molecular weight of approximately 10,000 was irradiated at a dose rate of 3.5×10^5 rads per hr for 2 hr. A concentration of 2.1 free radicals per polymer molecule was produced. This concentration corresponds to 42×10^{-3} free radical per monomer unit. This is six times the free-radical concentration per monomer unit found in the case of polymethylmethacrylate

C-5 and C-6

and gives a first indication of the effect of structure of the polymer on the storage of free radicals. This polymer has also been grafted. The results will be reported next month.

Work was begun on peroxy-induced grafting. Oxygen was bubbled through solutions containing 10 per cent polymethylmethacrylate during irradiation at a dose of 2.3×10^5 rads per hr. After 4 hr, 1.9×10^{-3} equivalents of peroxide per monomer unit were formed. Doubling the time to 8 hr increased the concentration to 2.57×10^{-3} equivalents of peroxides. These samples were grafted with vinylpyrrolidone and fractionated. The results will be available in the next report.

During the month of May work will continue along the dual lines described above. In particular, the effects of monomer concentration and solvents will be investigated.

Nitration of Hydrocarbons

M. J. Oestmann, J. F. Kircher, R. E. Fulmer,
and G. A. Lutz

This is the first monthly report on a new project, "The Effect of Phase on the Radiation-Induced Nitration of Hydrocarbons", initiated in April.

The objective of this research program is to study the effect of gamma radiation on nitration reactions in the nitric acid-cyclohexane system. This system will be irradiated in both the liquid and vapor phase. The nitration reaction will be studied over a range of temperature, pressure, and nitric acid concentration. All irradiations will be conducted in Battelle's cobalt-60 facility.

Vapor-phase nitration of aliphatic and alicyclic hydrocarbons proceeds by a free-radical mechanism at temperatures of about 400 C. Liquid-phase nitration is not controlled by a free-radical mechanism. In the presence of radiation it is expected that the nitration reaction will be initiated at a lower temperature. The nature and amount of nitration products produced during irradiation will depend on phase, temperature, pressure, and nitric acid concentration. It is expected that this study of the nitric acid-cyclohexane system will define the role played by the nonradiation parameters in the radiation-induced nitration reaction. Results from this study should find considerable application in many areas of radiation chemistry of interest in commercial radiation processing.

During April the design of a stainless steel irradiation vessel and furnace for static irradiation experiments was completed. Construction of this apparatus will be initiated in May. Several preliminary irradiations of the nitric acid-cyclohexane system in a glass vessel are being conducted to establish procedures for the chemical analysis of the nitration products. The analysis of the products from one irradiation completed in April is under way.

D-1

D. PROCESSING OF FEED MATERIALS

E. L. Foster

National Lead of Ohio (NLO) in operating the Feed Material Production Center, fabricates uranium fuel slugs from large vacuum-induction melted uranium ingots. Since the qualities of the fuel slugs are related, to some extent, to the qualities of the large uranium ingot, NLO has a real interest in the factors that play a role in ingot quality. A program now in progress at Battelle seeks a convenient method of examining the factors that are present in the casting step of the fabrication procedure. Improvements are desired in both present and future casting procedures.

Solidification of Uranium

E. L. Foster, C. K. Franklin, B. L. Fletcher,
A. B. Pritsker, and R. F. Dickerson

The manner in which uranium metal solidifies in cylindrical graphite molds is being studied. A mathematical model has been formulated to calculate the heat flow with time and predict the progress of the solidification within the casting. Since some thermal properties of the material involved were unknown at the temperature of solidification, these determinations were included as part of the over-all program.

Ingots 3 in. in diameter by 20 in. long have been cast to study the events occurring at the mold-metal interface during the cooling period of the ingot. Additional 3-in. castings were made to record the time-temperature history of the mold, metal, and furnace environment during this period. The thermal data so gathered will be used to refine and compare with the results from the mathematical model.

Current work has been concerned with the events taking place between the mold and ingot surface as solidification occurs in production-size uranium castings. These experiments are being conducted at the Feed Materials Production Center. To study the mold-metal interface, electrical probes were spaced 2 in. apart along the length of the mold and flush with its inner surface. The probes were attached to operation-type recorders operating off an 8-volt transformer. The probes were placed in such a manner that the pouring time and the time and position of the ingot-mold wall separation were accurately described. Three ingots, 7 in. in diameter by 48 in. long, were cast with the probes in position.

Initial data from the full-scale castings are being examined for evidence as to the thickness of the casting wall at the time separation occurs, because this factor is important in determining the proper casting-wall cell sizes, and has considerable influence upon the maximum allowable time interval used in computing the finite changes of temperature. The existing mathematical model contains the assumption that separation at the mold-casting interface occurs when the outer casting-wall cell solidifies. If this wall is relatively thick when separation is complete, the internal cell sizes must be redimensioned. This may have an adverse effect in that excessive computer time may be required for solution.

D-2

A second series of three ingots will be poured to measure mold, metal, and furnace temperatures during the freezing period. About 30 thermocouples will be placed in and on the mold to record temperatures. Additional thermocouples will be placed above and below the mold and on the furnace wall to measure environmental conditions. One casting has been poured.

E-1 and E-2

E. SPRAY DEPOSITION OF CALCIUM METAL ON NICKEL OR INCONEL

R. M. Evans and R. E. Monroe

This study is to determine the feasibility of coating nickel and nickel alloys with calcium by the arc-spraying method.

All of the research effort during April was directed toward overcoming the problem of white "oxide" formation during arc spraying. This oxide fills the spray chamber, prevents observation of the arc and the work, and also soils the surface to be coated in a very few seconds. It was found impossible to prevent this material from forming when using the device which pushes the wire into the spray chamber through two small holes. It was believed that the 0.0625-in. wire moving through the 0.078-in. -ID tubing pumped air into the argon-filled chamber. To check this conclusion, the entire spraying and wire-drawing mechanism was placed in an inert-gas welding chamber. The chamber was evacuated and filled with argon before spraying with argon. The white vapor also formed under these conditions. Therefore, the gas was changed to helium. With a helium atmosphere in the welding chamber and helium as the spraying gas, a black vapor forms very rapidly which also prevents proper mechanical operation of the process. The black vapor is apparently finely divided calcium metal. It oxidizes to a white powder as soon as the chamber is opened to air.

In view of the results reviewed above, it is planned during the next few weeks to make a few critical experiments to clarify the experimental work.

F-1

F. RESEARCH FOR AEC REACTOR DEVELOPMENT DIVISION PROGRAM

S. J. Paprocki and R. F. Dickerson

REACTOR MATERIALS AND COMPONENTS

R. F. Dickerson

In an attempt to reduce the amount of trivalent La_2O_3 or Y_2O_3 additive needed to stabilize UO_2 , ternary additions of divalent CaO have been studied. Most ternary compositions examined to date do not compare in oxidation resistance to the La_2O_3 or Y_2O_3 binaries although they are obviously better than UO_2 alone. One exception to this has been the composition UO_2 -22 mole per cent La_2O_3 -21 mole per cent CaO . This alloy was comparable in performance to the binary oxide systems. Continuing work has shown that CaO does not stabilize the rare-earth Type C structure in the solid solutions. As a part of the study concerned with high-temperature high-pressure solid-state studies, samples of U_3O_8 - BeO and UO_2 - Sc_2O_3 were subjected to pressures in excess of 100,000 atm at temperatures to 1500 C. No reactions were observed that would indicate formation of solid solutions or compounds. At a 120,000-atm pressure and 1130 C, the gamma high-pressure phase of U_3O_8 was found coexistent with a cubic structure having a lattice parameter of 5.40 Å.

Two capsules containing zirconium-2 w/o uranium alloy hydride specimens have been irradiated in the MTR and will be returned to the Battelle Hot Cell Facility for postirradiation examination during the month of May.

The eight "cold" capsules containing Type 347 stainless steel continue to be irradiated in high-flux positions in the ETR. Based on the analysis of dosimeters exposed during Cycle 13a, it is estimated that the first two capsules to be studied will be opened in June, 1960, with an estimated total exposure of 0.61×10^{26} nvt. Joint radiochemical analyses of nickel dosimeter wires are being performed at Battelle and by Phillips Petroleum Company personnel at the ETR. The Phillips results are about 30 per cent higher for the same wires. An effort is being made to resolve this difference in the cobalt-58 standardization. A second four-hole core-filler piece is being machined at Battelle for use with the gamma-heat capsules.

The investigation of niobium-base alloys for possible use as an alternate cladding in future EBR cores is continuing. Binary alloys of niobium containing 1 w/o chromium, 2 w/o chromium, and 4.5 w/o zirconium and ternary niobium-base alloys containing 10 w/o tantalum-2 w/o chromium and 20 w/o titanium-1.5 w/o chromium have been melted and fabricated. Hardnesses were determined after the various fabrication operations and heat treatments. Tensile specimens are being prepared, and thermal conductivities will be determined. Niobium-base alloys are also being studied for possible service in pressurized-water reactors. A niobium-base binary containing 45 a/o zirconium and a ternary containing 25.5 a/o titanium-6 a/o chromium exhibit total weight gains of 0.38 and 0.04 mg per cm^2 , respectively, after 140 days in 680 F water. There are also a number of alloys having total weight changes ranging from

-0.5 to +0.5 mg per cm², after a similar exposure. These alloys exhibit adherent films. Slabs cut from double consumable-electrode melted ternary alloys containing 10 a/o zirconium-10 a/o vanadium, 6.25 a/o zirconium-12.5 a/o vanadium, and 10 a/o titanium-5 a/o chromium have been successfully fabricated.

Oxide films which form on molybdenum under several conditions in sodium were identified, and friction studies of a molybdenum ball and plate under sodium have been initiated.

Valence Effects of Oxide Additions to Uranium Dioxide

W. B. Wilson, A. F. Gerds, and C. M. Schwartz

The purpose of this project is to investigate the effects of oxide additions to uranium oxide with regard to stabilizing the UO₂ fluorite structure under both oxidizing and reducing conditions. UO₂ when heated in an oxidizing atmosphere will transform to U₃O₈, which exhibits appreciable vapor pressure at temperatures above 1000 C. Previous work has shown that with additions of the rare-earth oxides, in particular, La₂O₃, and Y₂O₃, the fluorite structure may be retained under both oxidizing and reducing conditions, and a considerable reduction of vapor pressure is effected. Compositions of UO₂ containing 60 mole per cent of U₂O₃ or La₂O₃ were found to be superior from the standpoint of volatility and stabilization over other compositions.

Past work has been directed toward obtaining an understanding of the effects of these oxide additions on the oxidation characteristics of the solid solutions. A hypothesis, based upon a mechanism of valence compensation, was advanced by which to explain observed behavior. Thus, a defect solid solution of fluorite structure is formed with UO₂ containing up to 60 mole per cent of La₂O₃. As the U⁺⁴ is converted to U⁺⁶ upon oxidation, sufficient La⁺³ is introduced to produce an average valence of +4 for the fluorite structure. These reactions may be approximated as:

The current objective, utilizing the hypothesis of valence compensation, is to reduce the large amount of additive required to produce a stabilized material. The approach used is to substitute CaO for La₂O₃, since divalent additives should be more effective than trivalent additives for compensation. A series of solid solutions of UO₂-Y₂O₃-CaO and UO₂-La₂O₃-CaO have been fabricated and evaluated in air oxidation. Table F-1 compares the relative air oxidation performance of some of these materials to UO₂ and to the binary additives.

Table F-1 shows that a body of UO₂ lost over 60 w/o due to volatilization in 3000 F air. By contrast, the solid solutions containing UO₂ with 60 mole per cent La₂O₃ or Y₂O₃ usually indicate a slight increase in weight due to oxidation. The UO₂-La₂O₃-CaO and UO₂-Y₂O₃-CaO samples examined to date have indicated relatively

F-3

poor oxidation characteristics, although they are obviously better than UO_2 alone. One exception to this has been the composition UO_2 -22 mole per cent La_2O_3 -21 mole per cent CaO , which exhibited both low volatility and dimensional stability and was comparable to the performance of the binary oxide systems. With this exception, the results suggest that the oxidation characteristics of the samples with CaO additions are poorer than the binary systems above. From this exploratory evaluation of the ternary additives the UO_2 -22 mole per cent La_2O_3 -21 mole per cent CaO material appears to be near a composition which may be competitive to the binary systems while requiring less additive.

TABLE F-1. RELATIVE STABILITY OF SOLID SOLUTIONS^(a) IN AIR OXIDATION AT 3000 F AS INDICATED BY WEIGHT CHANGE DUE TO VOLATILITY

Composition, mole per cent	Time at 3000 F, hr	Weight Gain ^(b) , per cent
UO_2	20	-62.70
UO_2 -60 Y_2O_3	20	0.02
UO_2 -50 Y_2O_3	20	-0.17
UO_2 -40 Y_2O_3	20	-0.90
UO_2 -54 La_2O_3	20	-0.14
UO_2 -52 La_2O_3	20	-0.58
UO_2 -34 La_2O_3	20	-4.50
UO_2 -22 La_2O_3 -21 CaO	20	1.71
UO_2 -30 La_2O_3 -5 CaO	20	-9.30(c)
UO_2 -40 La_2O_3 -5 CaO	20	1.50(d)
UO_2 -30 La_2O_3 -10 CaO	20	-3.90
UO_2 -20 Y_2O_3 -20 CaO	5	-5.60(c)
UO_2 -25 Y_2O_3 -15 CaO	5	-4.40(c)
UO_2 -30 Y_2O_3 -10 CaO	5	0.39(c)

(a) Tested as compacted cylindrical bodies.

(b) Minus sign indicates weight loss.

(c) Bodies crumbled upon oxidation.

(d) Cracked.

It was previously reported that the effect of CaO was to stabilize the rare-earth Type C structure in the solid solutions. Continuing work has shown that this result was due to impurities depositing on the surface of the samples. Examination of the interiors of several samples containing surface contamination disclosed the fluorite phase. Upon extensive oxidation only the fluorite phase is found on the surface of the solid solutions, and the lattice parameter is observed to decrease. Chemical analysis has been initiated to determine the nature and source of the impurity and its possible effect upon the oxidation.

Electrical measurements of UO_2 -2, -10, and -20 mole per cent La_2O_3 were continued. The results indicated that the UO_2 -2 mole per cent La_2O_3 had the lowest resistivity to date, with increasing La_2O_3 content increasing the resistivity. The UO_2 -20 mole per cent La_2O_3 was too pyrophoric to permit any measurements.

Work will continue to fabricate and evaluate ternary compositions near that of the UO_2 -20 mole per cent La_2O_3 -20 mole per cent CaO composition.

High-Pressure High-Temperature Solid-State Studies

W. B. Wilson and C. M. Schwartz

The purpose of this project is to investigate the effects of combined high pressure and high temperature on solids, particularly those of interest for high-temperature-reactor components. A report, BMI-1328, has been issued which describes equipment, techniques, and some early results of studies in this area.

Following pressure calibration of the die several samples were subjected to pressures believed to be in excess of 100,000 atm at temperatures to 1500 C, using a platinum heater. No reaction has been observed to occur between U_3O_8 and BeO or UO_2 and Sc_2O_3 to form solid solutions or compounds. The structure of U_3O_8 was modified by the combined effects of high pressure and high temperature, as found previously. At a 120,000-atm pressure and 1130 C, the gamma high-pressure phase of U_3O_8 was found coexistent with a cubic structure having a lattice parameter of 5.40 A. Other samples, whose temperatures were uncertain due to failure of thermocouples, gave diffraction patterns of gamma U_3O_8 , of alpha U_3O_8 plus cubic, and of all cubic.

The tentative interpretation of the behavior of U_3O_8 at 120,000 atm is that at the lower temperatures the gamma phase is stable, as previously reported. Increased temperature is believed to offset the effect of pressure and the alpha modification is observed. At a still higher temperature, the cubic structure is found. The cubic structure is identical to that of U_4O_9 and is found at lower temperatures with increasing pressure. It is not clear whether the cubic structure actually is U_4O_9 or is, as presently believed, cubic with the composition nearer U_3O_8 , analogous to minerals such as pitch blende. Since the cubic U_4O_9 structure is the most dense oxide phase of uranium, pressure would tend to increase its stability, suggesting that, at pressures of the order of 150,000 atm, only the cubic phase will be found at these temperatures.

The difficulties in determining temperature are twofold. At extreme pressure, it is difficult to prevent thermocouple shorting, and gradients in the platinum heater are extreme, being of the order of 1000 C in a few millimeters. To improve this situation, the work was continued at 60,000 atm. In order to eliminate the extreme gradient, a BeO insert is placed inside the platinum heater, and is thermally insulated at each end. The high thermal conductivity of the BeO smooths out the gradient, resulting in marked improvement. The gradient problem is not as severe using graphite heaters, since the negative temperature coefficient of resistance and high thermal conductivity of graphite tend to automatically smooth out excessive gradients.

F-5

Work will continue to improve the temperature characteristics and to better define the U_3O_8 pressure-temperature phase diagram. The oxygen content of the cubic high-pressure phase will be determined by microbalance analysis to determine if reduction of U_3O_8 is occurring or if the cubic phase field extends to U_3O_8 at high pressure. Following this work, it is planned to use graphite heaters in an attempt to investigate possible reactions at higher temperatures.

Fueled Zirconium Hydride Moderator

H. E. Bigony, A. K. Hopkins, and H. H. Krause

The high-temperature X-ray diffraction study of the uranium-zirconium alloy hydrides containing 1 w/o and 25 w/o uranium has now been completed. The irradiation of the two capsules containing 2 w/o uranium alloy hydride has been terminated. Post-irradiation examination of the specimens will now be undertaken.

Structure and Pressure-Composition-Temperature Studies

All experimental work on this phase of the program has been completed. Both the hydrogen-absorption isotherms and the high-temperature X-ray diffraction studies are finished, and a topical report which will correlate the results of the two investigations is in preparation.

Radiation-Damage Studies

Capsule BMI-20-2 was discharged from the MTR during Cycle 121 shutdown (April 27, 1959). Together with Capsule BMI-20-1, which was discharged during Cycle 119 shutdown, it is being shipped to the Battelle Hot Cell Facility, where it will arrive early in May.

Temperatures in Capsule BMI-20-2 during the last cycle have been higher than the average previously recorded. The temperature at Thermocouple 1 was increased from about 1000 F to 1100 F, and that at Thermocouple 5 from about 1175 F to 1270 F.

Postirradiation examination of the specimens will be started in May. Fission-gas release will be determined, and, if the condition of the samples permits, density studies and metallographic examinations are planned also.

Irradiation Surveillance Program on Type 347 Stainless Steel

F. R. Shober, J. E. Howes, Jr., and J. F. Lagedrost

An evaluation is being made of the changes in the mechanical properties of AISI Type 347 stainless after exposure to a fast-neutron flux (neutrons having energies

F-6

>1 Mev) at approximately 120 and 600 F. This program is in support of in-pile loops at the ETR containing Type 347 stainless steel. The tensile cyclic-strain fatigue and impact properties are to be measured after each period of exposure representing 6 months of exposure of the KAPL C-33 loop in the F-10 position of the ETR. Since data on changes of mechanical properties of Type 347 stainless are available for exposures up to approximately 3.5×10^{21} nvt, the first 6-month interval will start after the above exposure has been obtained. Exposure for 3 years in the F-10 position is estimated to accumulate approximately 1.2 to 1.6×10^{22} n per cm^2 total neutron flux.

The eight "cold" capsules are being irradiated at process-water temperature and are located as follows: the K-8-NW position contains BMI-24-14 and BMI-24-16; K-8-SE contains BMI-24-4, BMI-24-8 and BMI-24-10; K-8-NE contains BMI-24-2 and BMI-24-6; and L-8-SE contains BMI-24-12. All capsules are so positioned to take advantage of the higher flux of each position. Prior to start up for ETR Cycle 13, fuel was inserted in the L-7 and M-7 positions. This additional fuel increased the flux density by approximately 40 per cent. The capsules were irradiated 18.5 days since the last report period. The total nvt shown in Table F-2 has been calculated on the basis of Cycle 13a dosimeters analyzed at the ETR. These values may be adjusted later after the analyses of dosimeters for Cycles 13b and 14 are complete.

A series of nickel dosimeter wires, irradiated in the K-8 position during Cycle 13a, has been analyzed at BMI. These results are shown in Table F-3. Two nickel wires were sent to Phillips Petroleum Company personnel (ETR) for cross calibration of cobalt-58 radioassay techniques. Their results were 30 per cent higher than BMI values for the same wires. An effort is being made to resolve this difference in the cobalt-58 standardization. Hence, flux data based on both cobalt-58 calibrations are reported in Table F-3. It should also be noted the values of total flux in Table F-2 are based on the Phillips data. The use of ammonium sulfate to determine the fast-neutron flux has been discontinued. Fast-flux values obtained from sulfur were quite low when compared with nickel irradiated in the same position.

A second, four-hole core-filler piece is being machined at Battelle. It will have holes for dosimeters in the center and in each of the four faces. A core-filler piece of this design should provide places for adequate dosimetry for the capsule to be irradiated at 600 F. Upon completion, the filler piece will be shipped to the ETR where it will be inserted into some position having a gamma flux of approximately 18 w per g of material.

A thermocouple-lead capsule, BMI-24-19, will be placed in one test position of the new core-filler piece after a gamma-flux profile has been determined. An attempt will be made to correlate temperature during irradiation as indicated by the lead capsule with the known gamma flux. In this way it is thought that an irradiation temperature of the nonlead capsules in a known gamma flux can be estimated.

Three nonlead capsules containing tensile and cyclic-strain fatigue specimens are being prepared. It is planned to use these capsules for some postirradiation annealing studies. It is thought that an anneal at 600 F after irradiation will produce materials that have property values between those of material irradiated at elevated temperatures and material irradiated at process-water temperature.

F-7

TABLE F-2. CUMULATIVE FAST FLUX ON "COLD" CAPSULES OF THE TYPE 347 STAINLESS STEEL
IRRADIATION-DAMAGE PROGRAM

Capsule	Specimen Type	Approximate Removal Date ^(a)	Approximate Exposure at Time of Removal ^(b) , 10 ²² nvt	Total Exposure as of April 20, 1959, 10 ²¹ nvt	
				Top	Bottom
BMI-24-2	Tensile and fatigue	Jan., 1962	1.31	1.827	2.625
BMI-24-4	Tensile and fatigue	Jan., 1963	1.78	0.862	1.957
BMI-24-6	Tensile and fatigue	June, 1961	1.08	2.703	2.013
BMI-24-8	Tensile and fatigue	June, 1962	1.54	0.988	2.018
BMI-24-10	Tensile and fatigue	Jan., 1961	0.84	2.081	2.527
BMI-24-12	Tensile and fatigue	June, 1960	0.61	2.850	2.162
BMI-24-14	Impact	June, 1962	1.54	2.596	2.655
BMI-24-16	Impact	June, 1960	0.61	2.628	2.581

(a) Based on 6-month lead on loop, plus 2 months for tests.

(b) Based on maximum fast flux at tube of 1.7×10^{14} nv for 8-month periods, 6-month lead time, and 2-month time for examination.

TABLE F-3. RESULTS OF ETR DOSIMETRY DURING CYCLE 13a AS DETERMINED AT BMI

Sample	Reactor Position	Distance From Top of Filler Piece, in.	Fast (>1 Mev) Flux, 10^{14} n./cm ² (sec)	
			Based on BMI Cobalt-58 Calibration	Based on ETR Cobalt-58 Calibration
BMI-7-1	K-8-W	2-3/8	0.41	0.53
-2	K-8-W	7	1.13	1.47
-3	K-8-W	11-5/8	1.55	2.02
-4	K-8-W	16-1/4	1.88	2.44
-5	K-8-W	20-7/8	2.02	2.63
-6	K-8-W	25-1/2	2.01	2.62
-7	K-8-W	30-1/8	1.76	2.29
-8	K-8-W	34-3/4	1.30	1.69
BMI-8	K-8-N	20-7/8	1.44	1.87
BMI-9	K-8-S	20-7/8	2.18	2.84
BMI-10	K-8-E	20-7/8	1.45	1.89

F-9

Development of Niobium-Base Alloys

E. Jablonowski, F. R. Shober, and R. F. Dickerson

Several niobium-base alloys are being evaluated for application as alternate cladding materials in future EBR cores. Alloys selected for study include niobium-1 w/o chromium, niobium-2 w/o chromium, niobium-4.5 w/o zirconium, niobium-10 w/o tantalum-2 w/o chromium, niobium-20 w/o titanium-1.5 w/o chromium, niobium-40 w/o titanium-10 w/o aluminum, unalloyed niobium, and a comparison alloy of vanadium-10 w/o titanium-1 w/o niobium (an acceptable alternate EBR cladding material). Melting, hot- and cold-fabricability studies, and metallographic examinations of the alloys have been completed.

Chemical-analysis data are reported in Table F-4. Alloys 2, 3, 5, and 7 retained a large amount of chromium, which had been overcharged to accommodate chromium losses by volatilization during arc-melting.

The hardness of the alloys was determined following various fabrication operations and heat treatments. The data are summarized in Table F-4. All alloying additions substantially increased the hardness of niobium, with chromium being the most effective addition. The data indicate that all the alloys were recrystallized after 1/2 hr at 1500 C and were subsequently stable at 900 to 1000 C for times up to 8 hr. The expected precipitation of NbCr₂ in Alloys 2 and 7 following solution treatment and annealing was not observed.

Tensile specimens of each alloy are being prepared for tests at 650 and 800 C. The thermal conductivity of the three alloys having the highest tensile strength at 800 C will be determined. Meanwhile, the sheet-to-sheet weldability of the cold-fabricable alloys will be studied.

Development of Corrosion-Resistant Niobium AlloysD. J. Maykuth, W. D. Klopp, R. I. Jaffee,
W. E. Berry, and F. W. Fink

The evaluation of selected niobium-base alloys for possible service in pressurized-water reactors was continued. Elevated-temperature property data are being accumulated on high-purity alloys to follow up screening hot-water corrosion tests which are being conducted on a series of commercial-purity niobium-base alloys. Additional high-purity alloys are being prepared to screen and evaluate new compositions of interest.

Commercial-purity niobium-base alloys have now been exposed a total of 140 days in 680 F water. The trends in corrosion behavior are similar to those reported in BMI-1324 and BMI-1330. A 45 a/o zirconium binary and a 25.5 a/o titanium-6 a/o chromium ternary continue to be the most corrosion resistant of the alloys tested, exhibiting adherent tarnish films and total weight gains of 0.38 and 0.04 mg per cm²,

TABLE F-4. CHEMISTRY AND HARDNESS OF NIOBIUM-BASE ALLOYS

Alloy	Alloy Composition, w/o		Rockwell B Hardness ^(b)				
			Upset Forged at 1370 C	Cold Rolled ^(c) 70 to 80 per cent	Vacuum Annealed		
	Nominal	Analyzed ^(a)			1/2 Hr at 1500 C, Furnace Cooled ^(d)	8 Hr at 900 C ^(e)	8 Hr at 1000 C ^(e)
1	Unalloyed Nb	99.7 Nb	72	81	24	<20	<20
2	Nb-1 Cr	1.84 Cr	89	102	78	77	82
3	Nb-2 Cr	3.21 Cr	98	(f)	(f)	(f)	(f)
4	Nb-4.5 Zr	4.33 Zr	87	96	64	72	70
5	Nb-10 Ta-2 Cr	9.95 Ta-3.31 Cr	100	(f)	(f)	(f)	(f)
6	Nb-40 Ti-10 Al	39.8 Ti-10.6 Al	106	>110	102	108	104
7	Nb-20 Ti-1.5 Cr	20.5 Ti-4.28 Cr	100	107	98	98	98
8	V-10 Ti-1 Nb	11.7 Ti-3.07 Nb	95	102	90	85	87

(a) Balance niobium except for Alloy 8, where the balance is vanadium.

(b) Average of five readings.

(c) Following upset forging.

(d) Annealed after cold rolling; furnace cooled in 1 to 2 min.

(e) Air cooled; alloys annealed in evacuated stainless steel tubes.

(f) Not available.

F-11

respectively. On the other hand, unalloyed niobium and binary alloys containing 2.5 a/o molybdenum or 5 or 10 a/o tungsten exhibited adherent films in initial exposures, but eventually the film spalled and the alloy samples lost weight at linear rates. A number of alloys are covered with relatively adherent dark-gray films and have total weight changes ranging from -0.5 to +0.5 mg per cm² after 140 days of exposure. The binary alloys in this category are: 10 to 35 a/o zirconium, 5 to 7.5 a/o molybdenum, 5 to 25 a/o vanadium, 5 a/o iron, and 10 to 35 a/o titanium; the ternary alloys are: 7.5 to 19.5 a/o titanium-0.5 to 2.5 a/o chromium, 10.5 to 21.5 a/o titanium-3 to 6 a/o molybdenum, and 10.5 to 24 a/o titanium-3 to 11 a/o vanadium.

Corrosion studies are being continued on high-purity niobium-base alloys exposed in 600 and 680 F water and 750 F 1500-psi steam. Corrosion results for binary alloys containing 7.18 a/o molybdenum and 12.58 a/o vanadium and ternary alloys containing zirconium-titanium and titanium-molybdenum are presented in Table F-5. After exposure times ranging up to 56 days, all ternary alloys and the 12.58 a/o vanadium binary exhibit adherent films at all test temperatures. The reaction rates for the vanadium alloy appear to follow the cubic rate law, while those of all other alloys more nearly approach a parabolic rate.

Additional creep data on some of the alloys were obtained and are summarized in Table F-6. The 12.58 a/o vanadium alloy continues to show the most resistance to creep at 1200 F of the alloys thus far tested.

Slabs cut from double consumable-electrode melted ingots of the alloys listed below were successfully rolled to 60-mil-thick sheet in evacuated stainless steel packs at 1800 F. These strips are being surface ground preparatory to annealing. Samples of each alloy will be prepared for room- and elevated-temperature mechanical-property testing as well as for corrosion tests in 600 and 680 F water and 750 F steam.

Alloy	Nominal Alloy Content (Balance Niobium), a/o	As-Cast Hardness, BHN	Quality of Sheet
NL-8	10 Zr-10 V	228	Fair: moderate edge cracking, one end split severely
NL-9	6.25 Zr-12.5 V	237	Good: light edge cracking
NL-10	10 Ti-5 Cr	196	Good: light edge cracking

Fabrication of the forty 50-g niobium-base alloys listed in Table F-7 was also completed. These alloy compositions were selected on the basis of their favorably low cross sections as well as the results of the early 680 F water corrosion-test results. The unalloyed niobium and binary alloy ingots containing up through 1 a/o zirconium, 25 a/o titanium, 5 a/o chromium, and 2.5 a/o vanadium were rolled to 45-mil-thick strip of excellent quality by alternate processes of cold rolling and vacuum annealing. The 2.5 a/o zirconium alloy cracked severely during attempted cold rolling and will be replaced for fabrication by hot-pack-rolling techniques. The balance of the alloys listed were rolled to 60-mil-thick strip in evacuated stainless steel packs at 1800 F.

TABLE F-5. CORROSION DATA FOR ALLOYS PREPARED FROM HIGH-PURITY NIOBIUM

Nominal Alloy Content (Balance Niobium), a/o	Total Weight Change ^(a) , mg per cm ²		
	600 F Water	680 F Water	750 F Steam
	<u>56 Days of Exposure</u>		<u>56 Days of Exposure</u>
Unalloyed commercial Nb	+2.23	(b)	(c)
Unalloyed high-purity Nb	+1.08	+1.77	-3.48
7.18 Mo ^(d)	+0.23	+0.61	-0.90
12.58 V ^(d)	+0.19	+0.22	+0.42
	<u>42 Days of Exposure</u>		<u>28 Days of Exposure</u>
45 Zr-5 Ti	+0.10	+0.34	+0.76
17.8 Ti-8.9 Mo	+0.13	+0.19	+0.33
10 Ti-3 Mo	+0.20	+0.24	+0.45

(a) Average of two specimens.

(b) Completely oxidized after 56 days of exposure.

(c) Completely oxidized after 28 days of exposure.

(d) Actual chemical analysis.

TABLE F-6. CREEP DATA ON HIGH-PURITY NIOBIUM-BASE ALLOYS TESTED IN VACUUM AFTER VACUUM ANNEALING 1 HR AT 1500 C (2730 F)

Alloy	Alloy Content (Balance Niobium), a/o	Test Temperature, F	Load, psi	Total Deformation at Time Indicated, per cent									Minimum Creep Rate, per cent per hr	Remarks
				On Loading	1 Hr	10 Hr	50 Hr	100 Hr	200 Hr	300 Hr	400 Hr	500 Hr		
NL-2	12.58 V	1200	30,000	0.20	0.21	0.21	0.21	0.21	0.21	0.21	0.21	0.21	Nil	Discontinued after 500 hr
NL-3	7.18 Mo	1200	30,000	0.19	--	0.21	0.26	0.30	0.35	0.39	0.41	--	0.00012	Discontinued after 431 hr
NL-4	46.8 Zr-5.06 Ti	1200	30,000	0.26	0.28	0.32	0.58	--	--	--	--	--	0.0035	Ruptured at 68.3 hr, 3 per cent elongation
NL-7	11.2 Ti-3.2 Mo	1200	20,000	0.25	--	0.26	0.27	0.28	0.29	0.30	0.31	0.32	0.00010	Discontinued at 500 hr
		1200	30,000	2.41	2.41	2.41	2.41	2.41	2.41	--	--	--	Nil	Stress increased to 35,000 psi at 210 hr
			35,000 ^(a)	3.56	3.82	3.82	3.82	3.83	--	--	--	--	0.000018	Discontinued after 120 hr under 35,000 psi

(a) Deformation values at 35,000 psi include 2.41 per cent total deformation incurred during 210-hr exposure at 30,000 psi.

F-13

Good-quality strip was obtained from all ingots excepting the 35 a/o zirconium-15 a/o aluminum, 35 a/o zirconium-5 a/o chromium, and the 45 a/o zirconium-5 a/o iron alloys (Alloys N33, N36, and N39, respectively, in Table F-7), which fragmented severely during rolling. The hot-rolled strips from all, excepting the latter three, alloys are being surface ground and annealed. Samples of each alloy will be corrosion tested in 680 F water and measured for hot hardness at temperatures up through 1650 F.

Rubbing Surfaces in Sodium Environments

J. W. Kissel, C. M. Allen, and W. A. Glaeser

A program of research designed to secure a basic understanding of the parameters involved in the friction and wear behavior of rubbing surfaces lubricated by high-temperature sodium is in progress. It is expected that results from this research will lead to the establishment of general principles and recommendations which can be applied to the design of sodium-cooled-reactor components. The current phase of this program is concerned with a detailed study of surface-film formation and interaction between rubbing specimens.

During April, oxide films which form on molybdenum under several different conditions were identified, and friction studies between a ball and plate, both molybdenum, were begun. Of the three sources of molybdenum available to make flat specimens, metallographic comparison indicated the hot-rolled (one direction only) molybdenum plate contained the least amount of inclusions. The hot-rolled material, therefore, has been chosen for use in static and rubbing experiments. Previous friction experiments have indicated a possible chemical or physical change in the molybdenum specimen surfaces at temperatures above 500 F. To investigate this, an attempt is being made to identify the surface films which are formed on molybdenum in the as-lapped and heat-tinted conditions. Electron-diffraction analysis indicates that the amorphous layer thought to exist as a result of surface finishing is replaced by or covered over by a MoO_3 film when the specimen is heated for several hours in air at about 575 F. This oxide film exhibits an orientation which is assumed to be a function of the rolling texture of the molybdenum substrate. When reheated in a vacuum overnight at 800 F, this film reverts to a MoO_2 composition. The latter composition also results when lapped surfaces are heated overnight to 400 and 800 F without the previous heating in air. In these experiments the vacuum heating was performed under forepump vacuum only, about 1×10^{-2} mm of mercury, absolute. When repeated under much higher vacuum conditions, 5×10^{-6} mm of mercury, absolute, the results were the same except after the 800 F heating, the electron-diffraction pattern was very diffuse and faint, and might represent metallic molybdenum. Heating lapped molybdenum surfaces in air for several hours at about 1100 F produces a voluminous reaction product which has been identified by X-ray diffraction as MoO_3 .

Concurrently with the studies of the surface films formed on static molybdenum surfaces, an extensive series of friction runs have been completed for dry surfaces in vacuum and in argon, over a temperature range from 80 to 1300 F. These experiments include both lapped and etched surfaces. The data from these friction runs have not yet

F-15

TABLE F-7. COMPOSITIONS, THERMAL-NEUTRON-ABSORPTION CROSS SECTIONS, AND HARDNESSES OF 50-G HIGH-PURITY NIOBIUM-BASE ALLOYS

Alloy	Nominal Alloy Content (Balance Niobium), a/o	Cross Section, barns per atom	As-Cast Hardness, VHN
N1	100 niobium	1.15	95 ^(a)
N2	1 zirconium	1.14	129
N3	2.5 zirconium	1.13	151
N4	5 zirconium	1.10	173
N5	10 zirconium	1.05	207
N41	25 zirconium	0.91	264
N42	35 zirconium	0.81	279
N6	40 zirconium	0.76	276
N43	45 zirconium	0.72	266
N8	65 zirconium	0.52	212
N9	75 zirconium	0.42	193
N10	90 zirconium	0.27	304
N11	2.5 titanium	1.25	98
N12	10 titanium	1.60	122
N13	25 titanium	2.30	146
N14	1 chromium ^(b)	1.17	84
N15	5 chromium ^(b)	1.25	90
N16	2.5 vanadium	1.22	106
N17	2.5 zirconium-5 vanadium	1.29	101
N18	25 zirconium-5 vanadium	1.10	283
N19	35 zirconium-5 vanadium	1.00	297
N20	45 zirconium-5 vanadium	0.90	304
N21	10 zirconium-5 titanium	1.24	202
N22	25 zirconium-5 titanium	1.10	258
N23	25 zirconium-15 titanium	1.56	253
N24	25 zirconium-25 titanium	2.04	253
N25	35 zirconium-5 titanium	1.00	262
N26	35 zirconium-15 titanium	1.50	264
N28	45 zirconium-5 titanium	0.92	253
N29	10 zirconium-5 molybdenum	1.13	236
N30	35 zirconium-5 molybdenum	0.88	323
N31	45 zirconium-5 molybdenum	0.78	321
N32	35 zirconium-5 aluminum	0.76	325
N33	35 zirconium-15 aluminum	0.68	429
N34	45 zirconium-5 aluminum	0.67	311
N35	10 zirconium-5 chromium ^(b)	1.14	194
N36	35 zirconium-5 chromium	0.99	312
N37	45 zirconium-5 chromium	0.93	330
N38	10 zirconium-5 iron	1.12	266
N39	45 zirconium-5 iron	0.78	348

(a) Anticipated hardness was 80 to 82 VHN; a value of 95 VHN indicates some contamination during melting.

(b) High weight losses in melting indicate that little or no chromium was retained in ingot.

been fully reduced; however, the coefficients of kinetic friction fall within the range of 0.3 to 1.2. The broad spread of friction values for repetitive slides at a given set of environmental conditions appears to be narrowed considerably following overnight conditioning at 1000 F and in a 5×10^{-6} mm of mercury vacuum.

Work planned for the remainder of this phase of the program is as follows: the surface-film studies and friction studies will be continued and expanded to include the effects of molten sodium on the test surfaces. Electron and light microscopy will be used to study and picture the molybdenum surfaces and the wear tracks produced by friction experiments. Differential thermal analysis will be employed to explore possible chemical reactions throughout the temperature range.

STUDIES OF ALLOY FUELS

R. F. Dickerson

A thorough examination of the fabrication of the niobium-30 w/o uranium alloy is being accomplished. Evaluation of the data thus far indicates that fabrication above 2550 F will not work the structure. The alloy is very sensitive to cracking during the initial breakdown period but once initial breakdown is accomplished additional fabrication should be readily achievable. There is no evidence to indicate that the purity of the base niobium used for these studies has any effect on the fabrication characteristics. Binary alloys containing 10, 20, 30, 40, 50, and 60 w/o uranium have been exposed to 600 and 680 F water for 1 week. Although there are insufficient data at this time, the weight gains appear reasonable. The 90 per cent niobium alloy has an ultimate tensile strength of 72,900 psi at room temperature, while the 80 per cent niobium alloy exhibits a strength of 90,200 psi.

Recrystallization studies of thorium-5 to 20 w/o uranium alloys show that, at 700 C, 80 per cent cold-reduced material softens only slightly after 5 min at temperature. Metallographic examinations of thorium-10 w/o uranium-2 w/o niobium and thorium-20 w/o uranium-4 w/o niobium alloys water quenched from 800 C and heat treated at 500 C for various times ranging from 4 to 200 hr failed to indicate transformation of the gamma-uranium alloy particles.

Development of Niobium-Uranium Alloys

J. A. DeMastry, F. R. Shober, and R. F. Dickerson

Potentially good reactor fuels, the niobium-rich uranium alloys, have not received proper consideration due to the lack of information concerning fabrication characteristics and physical and mechanical properties. To obtain such information niobium-rich uranium alloys were prepared and are being evaluated.

F-17

In order to determine what effect the major impurities, oxygen and zirconium, have on the properties of uranium-niobium alloys, three grades of niobium were used in alloy preparation: one containing 0.7 w/o zirconium and 600 ppm oxygen, a second containing 0.17 w/o zirconium and 700 ppm oxygen, and a third containing less than 200 ppm zirconium and less than 300 ppm oxygen. The alloys being studied are uranium-40, -50, -60, -70, -80, and -90 w/o niobium; each of these alloys has been prepared using all three grades of niobium. The uranium-80 and -90 w/o niobium alloys have been successfully fabricated into slab material.

A thorough examination of the fabrication behavior of the uranium-70 w/o niobium alloy is being made. Several different methods of fabrication and fabrication temperatures have been tried on this alloy. The first approach was to press forge at 2400 F. The alloy was fabricated in a molybdenum tube having a 1/4-in. -thick wall with molybdenum core plates welded onto each end. Approximately 700 tons of pressure was applied on the 2-1/2-in. -diameter specimen. The sample was reduced 69 per cent but was severely fractured in the process. Examination of the material after fabrication showed that the cracks appeared to have originated in the center of the ingot and to have propagated radially to the edges. Examination of the microstructures indicated that the cast structure was starting to break up. The material obtained was not sound, making hardness measurements difficult. Hardness readings and metallographic examinations of the material as cast, as press forged at 2400 F, and as annealed at 1832 F for 24 hr indicated that 2400 F was slightly below the hot working temperature for this alloy.

A second specimen of uranium-70 w/o niobium was upset hammer forged at 2550 F (protected by a molybdenum can). This produced much better results than obtained by press forging. The specimen showed cracks radiating from the center but not as severe as those of the press-forged material. Examination of the microstructure indicated that the reduction during fabrication, approximately 80 per cent, was sufficient to initiate recrystallization and grain growth at 2550 F. Annealing at 1832 F for 24 hr produced a more completely recrystallized structure. Hardness measurements before and after annealing were similar, indicating that the alloy was being hot worked. It was thought that a higher fabrication temperature might improve the fabrication characteristic of this alloy.

Two ingots were fabricated at 3000 F by upset hammer forging. The molybdenum can protecting one ingot ruptured after the ingot had been reduced about 15 per cent. A second ingot was forged to a 75 per cent reduction. Upon opening of the can it was found that the alloy had fractured into two pieces and showed evidence of severe edge cracking. Sound material was found on both sides of the fracture and out to the edges. The edge cracks did not extend into the material for any appreciable distance. The fracture appeared to have propagated radially. The microstructures of this alloy and hardness measurements indicated that the alloy was definitely hot worked. The ingot with the ruptured can is currently being examined closely to determine the reasons for the cracking during fabrication. This ingot showed severe surface cracking. A 1/4-in. section was cut from the top of the ingot and then another 1/4-in. section was removed. These surfaces are being polished to study the crack propagation. After polishing the surface is to be etched and re-examined for microcracking. A section will be examined for evidences of microporosity and impurities at grain boundaries. Evaluation of the

F-18

data obtained thus far indicates that the cracks are forming in the initial stage of the fabrication after which no further cracking occurs.

Two more ingots of uranium-60 and -70 w/o niobium have been prepared and attempts to fabricate them at 2600 F will be made. Very light reductions will be made on these alloys until a 30 per cent reduction has been obtained. It should be possible to make heavier reductions after the initial reduction has been made.

There has been no evidence to indicate that the purity of the base niobium has any effect on the fabrication characteristics of the alloys studied.

Table F-8 shows the results of oxidation of the uranium-niobium alloys at 572, 662, and 752 F. This study is incomplete at this time. All testing at 662 and 752 F will be conducted for a total time of at least 100 hr. The tests at 572 F will be run for a total time of at least 500 hr. In general, all alloys tested (uranium-60, -70, -80, and -90 w/o niobium) at 572 F exhibit good oxidation resistance; these alloy have an adherent black oxide casting. At 662 and 752 F, a brown spalling oxide is formed (in some cases as early as 20 hr), usually after 40 hr of testing. No appreciable difference in corrosion due to the use of different niobium as the base melting material has been noted.

Table F-9 shows 1-week corrosion data for uranium-niobium alloys in 600 and 680 F water. After 1 week most of the alloys appear to be showing very reasonable weight gains at 600 and 680 F. No effect of the different niobium bases is apparent after this short time at test. These tests will continue.

Table F-10 shows the results of corrosion testing of all uranium-niobium alloys in 750 F steam for 1, 3, and 7 days. No effect resulting from the use of different grades of niobium as base materials can be determined as yet. Corrosion testing of all alloys in CO₂ and NaK has been started but no results have been obtained.

Table F-11 shows the results of room-temperature tensile testing of the uranium-80 and -90 w/o niobium alloys. Tensile testing of remaining alloys at room temperature and high temperature (1600 F) will be accomplished as soon as specimen machining is complete.

No results have been obtained from the thermal-conductivity, electrical-resistivity, and thermal-expansion measurements.

A design of a high-temperature furnace for further fabrication studies has been made, and construction of the furnace has started.

Development of Thorium-Uranium Alloys

M. S. Farkas, A. A. Bauer, and R. F. Dickerson

Development of thorium-uranium-base alloys with improved irradiation-damage resistance and corrosion life is being sought by means of ternary and quaternary

F-19

TABLE F-8. CORROSION DATA FOR URANIUM-NIOBIUM ALLOYS IN AIR

Alloy Content (Balance Uranium), w/o	Air Corrosion Data for Indicated Times and Temperatures			
	186 to 471 Hr on Test at 572 F		60 Hr on Test at 662 or 752 F	
	Time at 572 F, hr	Weight Gain ^(a) , mg per cm ²	Weight Gain at 662 F ^(a) , mg per cm ²	Weight Gain at 752 F ^(a) , mg per cm ²
40 Nb ^(b, c)	--	--	1.4	12.5
40 Nb ^(d, c)	--	--	1.4	14.9
40 Nb ^(e, c)	--	--	1.5	17.6
50 Nb ^(b, c)	--	--	2.3	15.3
50 Nb ^(d, c)	--	--	6.9	14.0
50 Nb ^(e, c)	--	--	9.1	17.8
60 Nb ^(b, c)	--	--	5.8	17.4
60 Nb ^(d, c)	310	0.21	6.7	17.4
60 Nb ^(e, c)	310	0.71	5.5	16.3
70 Nb ^(b, c)	310	0.14	--	--
70 Nb ^(d, f)	442	0.25	--	--
70 Nb ^(e, c)	310	0.23	--	--
80 Nb ^(b, f)	442	0.33	1.0	10.8
80 Nb ^(d, f)	471	1.01	10.0	85.0
80 Nb ^(e, f)	471	0.45	8.75	63.0
90 Nb ^(b, f)	471	0.53	1.5	7.2
90 Nb ^(d, f)	442	0.29	0.5	13.0
90 Nb ^(e, f)	186	0.33	0.98	28.0

(a) Average of two specimens.

(b) Niobium contains 600 ppm oxygen and 0.74 w/o zirconium.

(c) Specimens prepared from a cast material.

(d) Niobium contains 700 ppm oxygen and 0.17 w/o zirconium.

(e) Niobium contains less than 300 ppm oxygen and less than 200 ppm zirconium.

(f) Specimens prepared from fabricated material.

TABLE F-9. CORROSION DATA FOR URANIUM-NIOBIUM ALLOYS IN WATER AFTER 7 DAYS

Alloy Content (Balance Uranium), w/o	Total Weight Change After 7 Days in Water of Indicated Temperature ^(a) , mg per cm ²	
	600 F	680 F
40 Nb(b, c)	0.27	1.86
40 Nb(d, c)	0.31	0.57
40 Nb(e, c)	0.20	0.31
50 Nb(b, c)	0.24	0.83
50 Nb(d, c)	0.25	0.44
50 Nb(e, c)	0.26	0.38
60 Nb(b, c)	0.52	0.66
60 Nb(d, c)	0.29	0.46
60 Nb(e, c)	0.23	0.46
70 Nb(b, c)	0.31	1.00
70 Nb(d, f)	0.27	0.97
70 Nb(e, c)	0.31	0.50
80 Nb(b, f)	0.18	0.30
80 Nb(d, f)	0.25	0.43
80 Nb(e, f)	0.18	0.22
90 Nb(b, f)	0.12	0.28
90 Nb(d, f)	0.25	0.09
90 Nb(e, f)	0.29	-4.22

(a) Average of two specimens.

(b) Niobium contains 600 ppm oxygen and 0.74 w/o zirconium.

(c) Specimens prepared from as-cast materials.

(d) Niobium contains 700 ppm oxygen and 0.17 w/o zirconium.

(e) Niobium contains less than 300 ppm oxygen and less than 200 ppm zirconium.

(f) Specimens prepared from fabricated material.

F-21

TABLE F-10. CORROSION DATA FOR URANIUM-NIOBIUM ALLOYS
IN 750 F STEAM

Alloy Content (Balance Uranium), w/o	Total Weight Change After Indicated Time in 750 F Steam(a), mg per cm ²		
	24 Hr	72 Hr	168 Hr
40 Nb(b, c)	0.76	-0.29	-3.92
40 Nb(d, c)	0.28	-0.26	-2.83
40 Nb(e, c)	0.16	-0.70	-2.10
50 Nb(b, c)	0.56	0.23	-0.31
50 Nb(d, c)	0.28	0.14	-0.35
50 Nb(e, c)	0.28	-0.07	-1.30
60 Nb(b, c)	0.33	0.29	-0.02
60 Nb(d, c)	0.38	0.24	0.14
60 Nb(e, c)	0.29	0.47	0.49
70 Nb(b, c)	0.43	0.14	-0.59
70 Nb(d, f)	0.61	0.46	-1.65
70 Nb(e, c)	0.44	0.28	-1.80
80 Nb(b, f)	0.30	0.45	0.56
80 Nb(d, f)	0.36	0.62	0.77
80 Nb(e, f)	0.25	0.40	0.57
90 Nb(b, f)	0.25	0.36	0.51
90 Nb(d, f)	0.32	0.38	-1.45
90 Nb(e, f)	0.43	0.57	-0.43

(a) Average of two specimens.

(b) Niobium contains 600 ppm oxygen and 0.74 w/o zirconium.

(c) Specimens prepared from as-cast material.

(d) Niobium contains 700 ppm oxygen and 0.17 w/o zirconium.

(e) Niobium contains less than 300 ppm oxygen and less than 200 ppm zirconium.

(f) Specimens prepared from fabricated material.

TABLE F-11. ROOM-TEMPERATURE TENSILE PROPERTIES^(a)

Alloy Content (Balance Uranium), w/o	0.2 Per Cent Offset Yield Strength, psi	Ultimate Tensile Strength, psi	Elongation ^(b) , per cent	Reduction in Area, per cent
90 Nb ^(c)	57,200	72,900	30	53
80 Nb ^(d)	73,200	90,200	7	9

(a) Average of two specimens, specimens are in the as-forged conditions (2500 F).

(b) Gage length of 0.65 in.

(c) Niobium used contains 600 ppm oxygen and 0.7 w/o zirconium.

(d) Niobium used contains 700 ppm oxygen and 0.17 w/o zirconium.

F-23

alloying and process control. Additions of zirconium, niobium, or molybdenum are being studied; these elements are added for the purpose of strengthening the thorium matrix and stabilizing the gamma-uranium phase. The effects of various fabrication variables on the size and distribution of uranium particles within the thorium binary alloys are also being examined.

Studies performed on binary thorium-uranium alloys in the as-cast, hot-rolled, and cold-worked conditions indicate that the as-cast structure is important in determining the cold-worked structure. For instance, the induction-melted alloys showed uranium concentrated in the grain boundaries, the particles taking on the form of the boundary. In the arc-melted alloy the uranium generally exists as discrete particles within the matrix (as the uranium content increases more particles are found in the grain boundaries). On subsequent hot rolling and cold rolling these same structures persist. Inasmuch as a fine dispersion of uranium particles is believed desirable from the point of view of irradiation damage, it appears that the arc-melted material would be superior. Heat treatments of the induction-melted thorium-uranium alloys are being performed to find out if the as-cast structure can be altered so that a fine dispersion of uranium particles can be obtained.

Recrystallization studies of thorium-5 to 20 w/o uranium alloys show that at 700 C, 80 per cent cold-reduced material softens only slightly after 5 min at temperature; additional time causes no significant drop in hardness. It is not known whether or not actual recrystallization takes place. Density determinations by the displacement method on arc-cast and cold-rolled thorium are as follows: Ames thorium, 11.60 g per cm³; crystal-bar thorium, 11.71 g per cm³.

Metallographic examinations of thorium-10 w/o uranium-2 w/o niobium and thorium-20 w/o uranium-4 w/o niobium alloys, water quenched from 800 C and heat treated at 500 C for various times ranging from 4 to 200 hr, failed to indicate transformation of the gamma-uranium alloy particles. X-ray diffraction is being employed for a more certain appraisal of the transformation kinetics of the uranium-niobium particles.

FISSION-GAS RELEASE FROM REFRACTORY FUELS

J. Melehan, D. A. Vaughan, J. C. Smith,
R. Barnes, S. D. Beck, and F. A. Rough

The most important current problem in the use of UO₂ as a fuel is its release of fission gases at high temperatures. This program is intended to develop additional understanding of the important aspects of this problem as they occur in practical fuels.

The general scope of research includes characterization and study of gas release from sintered UO₂ bodies during postirradiation heating and during actual exposure to neutron flux in the BRR. Supplementing these studies, high-density UO₂ is being prepared for research into the nature and analytical description of diffusion in UO₂.

Diffusion in UO_2

Material for the accurate determination of diffusion coefficients in UO_2 should be free of porosity, grain boundaries, impurities, and unusual concentrations of defects. Single crystals would be ideal for this purpose and two lots of single-crystalline material are being evaluated for potential use. In addition, various methods of preparing large-grained high-density UO_2 are being studied in order to provide an alternate material. In some respects large-grained high-density material prepared from the same lot of UO_2 powder as the porous, sintered material to be characterized and studied would perhaps be as suitable or more suitable than single crystals.

The evaluation of a 5-lb lot of Norton fused single crystals of UO_2 has been largely completed, and there is a good possibility that the material will be useful. This UO_2 is prepared, presumably, by arc melting in air and has a surface layer of nitriles. The skin of the surface layer is UN_2 and the under layer has been identified as U_2N_3 . The bodies of the crystals contain numerous small inclusions which have not been positively identified but are probably UN or U_2N_3 . The amount of this contamination decreases toward the center of the crystals. In one case the second phase was identified as uranium and it seems likely that small but variable amounts of both nitride and uranium may exist in this material. Estimates of the oxygen-uranium ratio by X-ray diffraction vary, depending upon location in the crystals, from 2.004 to 2.03. An oxygen analysis gave a ratio of 1.99. Carbon and nitrogen contaminants ranged from 10 to 30 and 10 to 20 ppm, respectively, and the total metallic impurities amounted to about 200 ppm.

Several treatments intended to refine the material consisting of heating at 1500 to 2000 C in vacuum, in argon, or in hydrogen have been carried out. Additional heat treatments are being made; however, the most promising treatment to date has been slow heating to 1500 C in hydrogen and slow cooling. In subsequent treatments it is planned to heat to temperature, introduce hydrogen and hold for a fixed time, evacuate, and cool. The role of hydrogen is uncertain and a high vacuum may be just as effective. Both vacuum and hydrogen treatments will be tried.

Several small single crystals prepared by the Verneuil process and supplied by MCW are also being evaluated.

In addition, methods of preparing sintered oxide bodies of approximately theoretical density are being considered. Such material may be employed in studies of the effect of grain size on fission-gas-release rates. Compacts sintered to 94 per cent and 97 per cent of theoretical density at 1400 C and 1750 C were resintered at 2000 C in vacuum. The resintered densities were both 97 per cent of theoretical, indicating that for the particular material, in the pressed and sintered condition, very little densification is possible above 1750 C. Microstructures, however, are altered. As might be expected, there is considerable grain growth and coalescence of porosity, with pores changing from grain-boundary positions to positions in the oxide grains. It is expected that these microstructural changes will be of primary significance in characterizing the sintered specimens and also in developing a mathematical model for fission-gas release. Experiments have been planned to develop a high pressure-high temperature

F-25

technique for preparing sintered oxide of a variety of grain sizes at densities approaching the theoretical value. Similarly work has been initiated in the pressing and sintering of oxide pellets for ultimate use in fission-gas-release experiments.

Preliminary experiments consisting essentially of irradiation at low temperatures and heating in the radiochemical laboratory are expected to be initiated in May or early June. Detailed design of the necessary equipment has been completed, and construction of the apparatus is in progress.

Characterization of Sintered UO_2 and Model of Gas Release

From a practical standpoint one might conclude that the equivalent-sphere model for gas release from UO_2 , which is based upon surface-area measurements and calculation of an equivalent sphere size, is adequate. Preliminary comparison of this and other methods of representing diffusion from UO_2 indicates that this assumption is true if only a small fraction of the gas is diffused out under the conditions specified. Thus, if one has an accurate measurement of surface area which is determined by gas-adsorption techniques, one can expect the diffusion release of small amounts of gas from this surface area to the exterior to follow the mathematics of the equivalent-sphere model. If, however, significant amounts of gas are released by diffusion, the difference between the assumed model and the actual process of release begins to become important. As an example of this, the microstructure of a sample of UO_2 has been analyzed to determine the number, size, and distribution of pores. The data were represented reasonably well by a Mott-type distribution. Based on this, the specimen pore distribution was assumed to follow a Mott-type distribution strictly, and the pores were assumed to be interconnected in a manner that diffusion into the holes would result in release to the exterior. The same sample was represented by the equivalent-sphere model, and calculations of gas release were made for these two idealized cases. As one expects, for a given value of D and low releases of gas, the fractions predicted to be released are nearly the same. The predictions of the two models diverge, of course, as the amount of gas released increases, and at a 20 per cent release the corresponding calculated diffusion coefficients from the two models differ by a factor of three.

The objective of further consideration of the model of release is not the development of a new model as such but a better understanding of the applicability and limitations of any model that may be used. This consideration of the model of release, coupled with additional characterization studies, will, it is believed, provide a better insight into the true nature of the microstructure and pore structure of UO_2 materials.

Studies of characterization are in progress, including analyses of microstructure and pore structure, permeability and surface-area measurements, and other studies. Additional materials are presently being prepared or procured to provide UO_2 bodies having sufficient variations in structure or character as to give a basis for understanding the role of each of the microstructural features.

Another important aspect of the diffusion of gases in UO_2 is the role of defects, especially in irradiated samples. Thus, methods and techniques for better understanding of defect structure in UO_2 are being developed. One of the more promising methods consists of "decoration" of UO_2 by diffusing oxygen into samples to produce high oxygen concentrations along defects such as dislocation lines, and along grain boundaries or interconnected porosity. These sections decorated in this manner can then be studied by optical or infrared transmission, since the high-oxygen regions will tend to be opaque. Thin sections, 25 to 30μ , of UO_2 transmit visible light with a wavelength of about 6500 Å. Correlation of observations of defects by transmission methods and by etching techniques is planned, since a method of observation adaptable to routine use on irradiated samples is needed.

Preparations for In-Pile Study

One of the major problems for in-pile quantitative measurement and interpretation of gas release from UO_2 is the release of gas by fission recoil from the exterior surfaces. In addition, the passage of recoils through the surfaces of internal pores may have appreciable effects on gas release from the surfaces. A series of calculations of release rates by diffusion and by surface recoil has been made to give an understanding of the effects of UO_2 characteristics and temperature on the ratio of these releases. It appears that it will be practical to carry out experiments on ordinary sintered UO_2 bodies, if the temperature can be raised to perhaps 1300 C. The alternative is to allow the recoils to be imbedded in the surroundings but design these surroundings to have the same diffusion coefficient as UO_2 . Since the high temperatures are more important in fuel-element design for containment of released fission gases, the former approach is favored.

Design of a high-temperature apparatus for in-pile operation is largely completed, including both the in-pile components and gas-measurement train. Construction of the apparatus will begin in a few weeks.

GENERAL FUEL-ELEMENT DEVELOPMENT

S. J. Paprocki

Techniques are being developed for the fabrication of high-density cermet elements consisting of 60 to 90 volume per cent of UO_2 , UN, or UC combined with stainless steel or niobium. Niobium-coated UO_2 powder has been cold pressed and then densified to a theoretical density of 92.5 per cent by use of the gas-pressure-bonding process. This method of fabrication is attractive as the cermet is clad and densified simultaneously without use of a high-temperature sintering operation.

Ceramic fuels and niobium- and molybdenum-base cermet materials are being clad with molybdenum and niobium by use of the gas-pressure-bonding process. Solid-phase bonding of both of these metals has been achieved at temperatures above 2000 F and a helium gas pressure of 10,000 psi.

F-27

The final irradiation capsule containing dispersion elements consisting of 24 w/o UN and UC dispersed in stainless steel has been shipped to Battelle from the MTR. This capsule was in the MTR for four cycles, with the specimens operating in a temperature range from 1500 to 1700 F.

The gas-pressure-bonding process has proven to be a very effective and versatile process for bonding of fuel elements and assemblies. Techniques involving pretreatment of materials for bonding are being developed by essentially trial-and-error methods. In order to achieve an understanding of the mechanisms involved in pressure bonding, a more fundamental study of the bonding process is being conducted.

Fabrication of Cermet Fuel Elements

S. J. Paprocki, D. L. Keller, G. W. Cunningham,
and D. E. Kizer

Methods of producing cermets of 90 per cent of theoretical density or better containing 60 to 90 volume per cent ceramic fuel are being investigated. Evaluations of fabricated cermets are being made on the basis of microstructure and physical and mechanical properties.

A 0.5-in. -diameter cermet was pressed from UO_2 powder coated with niobium. The UO_2 powder was coated by vapor-deposition techniques to a thickness to obtain 20 volume per cent metal. The green cermet was fitted into a Type 304 stainless steel sheath prior to hydrostatic pressing for 3 hr at 2400 F under a helium gas pressure of 10,000 psi. The density was increased from a green density of 70.6 per cent of theoretical to 92.5 per cent of theoretical density after hydrostatic pressing. Microscopic examination of the core showed a continuous matrix of niobium metal, with no porosity. Since stainless steel was used for a sheathing material during hydrostatic pressing, iron had diffused into the niobium matrix of the cermet to the depth of 1 mil. The core was extremely brittle so that cracking occurred when an attempt was made to machine the sheath and diffusion layer from the cermet.

The modulus of rupture has been obtained on cermets fabricated by hot press forging. When possible, two 0.080 by 0.160-in. specimens were ground from each cermet, one having the 0.080-in. dimension parallel with the direction of hot press forging (designated longitudinal or L) and the other having the 0.080-in. dimension perpendicular to the direction of hot press forging (designated transverse or T). The specimens were broken over a span of 0.83 in. at room temperature. Table F-12 shows the results.

As has been reported in BMI-1330, oxygen diffusion from the niobium metal to the UN has been detected. This may have some effect upon the the UN-niobium cermet modulus of rupture reported in Table F-12.

TABLE F-12. MODULUS OF RUPTURE OR MAXIMUM STRESS IN TENSION ON BENDING 1-IN. -LONG CERMETS

Specimen	Composition, volume per cent	Density, per cent of theoretical	Modulus of Rupture, psi
57-1-L	80 UO_2 -Nb	91.9	7,500
57-1-T	80 UO_2 -Nb	91.9	14,200
53-1-L	80 UO_2 -Type 302B stainless steel	91.1	4,100
53-1-T	Ditto	91.1	4,000
53-2-L(a)	Ditto	91.3	3,400
53-2-T	Ditto	91.3	2,800
53-4-L(a)	Ditto	90.9	1,200
Ch-59-L	80 UN-Nb	90.6	34,200
Ch-59-T(a)	80 UN-Nb	90.6	4,600
63-1-L	80 UN-Type 302B stainless steel	90.5	26,500
63-1-T	Ditto	90.5	20,200
63-2-L	Ditto	86.0	25,600
63-2-T	Ditto	86.0	23 900

(a) Cracks were noted in specimens after machining.

At present, UO_2 cermet containing woven Nichrome screens are being prepared for pressure bonding. The rippled screens will be placed into a powder-compacting die to which minus 325-mesh UO_2 powder will be added prior to compacting. The purpose of this study is to determine the feasibility of obtaining bonding of the peaks of the rippled wire to the cover plates during bonding. If bonding occurs, this technique would offer an increase in thermal conductivity while adding strength.

Gas-Pressure Bonding of Molybdenum- and Niobium-Clad Fuel Elements

S. J. Paprocki, E. S. Hodge, R. W. Getz, and P. J. Gripshover

Cermet and ceramic-type fuels are being clad with molybdenum and niobium by the gas-pressure-bonding technique. These materials possess desirable properties for nuclear applications due to their high-temperature strength and favorable cross sections.

Niobium-clad specimens have been most satisfactorily bonded at temperatures between 2100 to 2300 F for 3 hr at 10,000 psi. These temperatures provide adequate flow, plastic deformation, and recrystallization for metallurgical bonding of flat plates, pieced components, and picture-frame fuel plates. Reaction between the cladding and container or intermediate barrier layers studied thus far results in some embrittlement of the niobium at these bonding temperatures. Partial metallurgical bonding was achieved at 2000 to 2100 F with surface preparations developed in the initial stages of the program for niobium. It now appears possible to bond with more recently improved surface-preparation techniques at the lower bonding temperatures and minimize the problem of the embrittling reaction encountered at the higher bonding temperatures.

F-29

In previous surface-condition studies, a pickling solution was developed that could be used to surface prepare niobium and obtain strong bonds with 60 per cent complete bond integrity. This solution is employed at 140 F and consists of 95 parts sulfuric acid, 4.5 parts nitric acid, and 0.5 part hydrofluoric acid to which 18.8 g per liter of chromic oxide has been added. It has now been determined that a follow-up treatment in cold water and saturated sodium hydroxide reduces the amount of contamination originally observed along the bond interface. Machined and belt-abraded surfaces have shown inconsistent results during bonding; however, it has been observed that the high-pressure points produced by surface roughness produced during machining or abrading bonded exceptionally well. The valleys did not bond well in the very rough surfaces and the formation of spherical voids along the bond interface was observed. The surface-roughness values studied in detail were 80 and 250 rms. Intermediate values will be studied to determine if the voids can be closed with an rms value of less than 250 and still achieve the excellent bonds obtained at the high points of stress on the rougher surfaces.

Contamination of the niobium by reaction with the can or spacer materials becomes increasingly severe with increased bonding temperatures above 2000 F. Metallic foils of tungsten, tantalum, molybdenum, and Fecral are not suitable as spacer materials for specimens bonded at these elevated temperatures. The use of graphite-coated niobium spacers between the specimen and the bonding container appears promising. No appreciable amount of carbon diffusion is observed during bonding for short times of 2 to 3 hr at 2200 F. Results of recent analyses indicate that it is necessary to outgas the coated spacers and bonding container at the bonding temperature in a vacuum prior to the assembly of the specimens for bonding.

Molybdenum specimens pressure bonded at 2400 to 2550 F have exhibited 40 to 50 per cent metallurgical bond integrity; however, these specimens are more brittle than the starting material. Molybdenum sheet was annealed at 2200, 2300, and 2400 F for 3 hr in molybdenum envelopes to determine the effect of temperature on embrittlement. The specimens annealed at 2300 and below did not suffer a loss in ductility, while the specimen treated at 2400 F was brittle; consequently, emphasis will be placed on developing surface preparation and employing longer bonding times in an attempt to achieve consistent metallurgical bonding at 2300 F.

The as-received arc-cast and fabricated molybdenum being used in this study is extremely brittle. To improve the initial ductility prior to bonding and increase the surface energy of the molybdenum, it has been found necessary to cold roll or warm and cold roll to a 4-to-1 reduction. This material will be used in the future studies with surface conditioning by machining, machine belt abrading, degreasing, pickling, and combinations of two or more of these techniques.

As is true for niobium, the reaction of spacer and can materials with molybdenum specimens introduces undesirable contamination and embrittlement. Metallic spacers, in general, are unsatisfactory since they alloy rapidly with either the specimen, the container, or both at temperatures in excess of 2200 F. Graphite-coated molybdenum and niobium have appeared promising in preliminary studies; however, additional evaluations are necessary to determine the extent of the carbon diffusion into the molybdenum. Flame-sprayed refractory coatings are being studied as a means of preventing reaction; also, window glass which is known to be compatible with molybdenum at bonding temperatures is being investigated as a separator material.

The Irradiation of UC- and UN-Stainless Steel
Dispersion-Type Fuel Elements

A. W. Hare and D. L. Keller

The purpose of this program is to irradiate dispersion fuel elements consisting of 24 w/o UN and UC dispersed in stainless steel and clad with stainless steel at elevated temperatures and compare the results with dispersion fuel elements consisting of UO_2 dispersed in stainless steel.

Twelve test specimens, six containing UN as fuel and six containing UC as fuel, are being investigated. Four specimens (two UN and two UC) each were irradiated in a single irradiation capsule. Two of the irradiation capsules have been irradiated and returned to Battelle for postirradiation examination and evaluation. The preirradiation and postirradiation dimension measurements and the burnups estimated by quoted fluxes and dosimetry data on the first eight specimens were reported in the two previous monthly progress reports. The metallographic examination of selected specimens from these first two capsules has been completed, and radiochemical analyses are in progress.

The final capsule (BMI-18-3) of this series was shipped from the MTR to the Battelle Hot Cell Facility on April 30. The four specimens (two UN-stainless steel and two UC-stainless steel) operated at core temperatures in the range of 1500 to 1700 F through four MTR reactor cycles.

Factors Affecting Pressure Bonding

G. W. Cunningham and J. W. Spretnak

An investigation directed toward the establishment of the mechanism and kinetics of solid-state bonding of metals by the application of heat and pressure is being conducted with specimens of copper, nickel, and zirconium.

A limited amount of work with copper has continued, although high-purity oxygen-free specimens are still not available. The OFHC copper has not been received, but electrolytic tough-pitch copper has been melted under a hydrogen atmosphere, and rolled to plate form. The rolled plate is being machined to 0.080-in. -thick specimens with one 500-rms shaped surface and one 8-rms ground surface.

Several specimens have been run to gain qualitative information concerning the method of applying pressure to the heated specimen. One specimen was pressed by increasing the pressure to 10,000 psi in 2,000-psi increments as the temperature increased from 900 to 1100 F. The total time involved was 35 min. In contrast to specimens pressed at 10,000 psi and 1100 F for 10 min, there were no void areas at locations most distant from the points of initial contact. The bond line was shaped as an irregular series of steps, indicating that void areas had been closed in a series of jumps corresponding to the increases in pressure rather than in a continuous manner. A

F-31 and F-32

second specimen was pressed at 1100 F for 2 hr at 10,000 psi, cooled, pressed at 25,000 psi at room temperature, the pressure was reduced to 10,000 psi, and the specimen was heated to 1100 F. As it heated, pressure due to the expansion of the copper gradually built up the total pressure to 15,000 psi at 1100 F. No void areas could be detected at 1000X, and, although the bond line was visible, it was no thicker and was similar in appearance to an ordinary grain boundary. A third specimen was given an identical treatment except that the pressure bonding at 1100 F and 10,000 psi was eliminated. Similar results were obtained except that the bond line was thicker than ordinary grain boundaries. A fourth specimen was pressed at room temperature at 80,000 psi and then heated to 1100 F under no application of pressure. A bond line similar to that obtained by pressing at 1100 F and 10,000 psi was obtained, i. e. , large void areas at points of poor contact and bond lines several times thicker than ordinary grain boundaries. Although the gradual application of pressure appears beneficial, additional tests are necessary to obtain an understanding of the mechanism. A series of specimens is being prepared and will be run with fewer variables.

Annealing studies are being conducted in an effort to gain information on the nature of the bond interface. The results are somewhat difficult to interpret due to the lack of high-purity copper. Increasing the temperatures from 1800 to 1900 F and increasing the times at 1800 F up to 18 hr have not greatly affected the grain structure at the bond line. Grains grow in size and in some cases obliterate the bond interface, but in many cases grain growth stops at the interface. In addition, there is some evidence that, during pressing, bonds of highly stressed metal are formed near the surface and at the interface of the specimens, with the more stressed areas being on the roughest surface at the interface. During annealing, nucleation and grain growth vary in the different layers. Annealing of specimens pressed by gradual application of pressure may eliminate some of these problems, since a more uniform stressing appears to occur. Annealed specimens of zirconium have not been examined as yet.

Nickel and nickel-copper specimens are being hot pressed for bonding studies.

FF-1

FF. FUEL-CYCLE PROGRAM STUDIES

GAS-PRESSURE BONDING OF CERAMIC, CERMET,
AND DISPERSION FUEL ELEMENTS

S. J. Paprocki, D. L. Keller, E. S. Hodge, C. B. Boyer,
J. B. Fox, and D. E. Kizer

The prime objectives of this program are to utilize the gas-pressure-bonding technique to reduce fuel-element manufacturing costs, while maintaining or improving the quality of the fabricated elements. The study will be concerned with the development of the gas-pressure-bonding process for the densifying and cladding, with stainless steel, of ceramic, cermet, and dispersion fuels.

The ceramic, cermet, and dispersion fuel systems were selected for this study because it is believed that these fuel systems offer the greatest potential for achieving a high burnup over a range of temperatures. The fabrication costs are low in comparison with other fuel systems, and, by the utilization of gas-pressure bonding, there is an excellent opportunity for making a substantial reduction in cost while improving performance. Stainless steel was selected as cladding because it is a low-cost and readily available material which is compatible with most gas and liquid-metal coolants and with most fuels. It is currently being considered as cladding in several of the civilian power-reactor programs.

The greatest effort in this program will be directed toward the development of Type 304 stainless steel-clad ceramic uranium dioxide fuel elements and assemblies of various shapes. Uranium dioxide is being used or considered by more power-reactor programs than any other material and the general results that are obtained with this fuel element should also be applicable to other ceramic fuels. A small effort will be directed to the development of uranium dioxide cermet and dispersion systems.

The initial phase of the study is concerned with the controlled densification of ceramic uranium dioxide fuel by gas-pressure bonding. Preliminary studies have shown that uranium dioxide can be highly densified by this technique, and it is believed that by the proper selection of oxide and gas-pressure-bonding parameters it will be possible to achieve almost any desired density. Investigations will be conducted to determine the effect of the bonding parameters of time, temperature, and pressure, and of pressure containers of various configurations on the densification of uranium dioxide fuel. The effects of particle size, density, porosity, stoichiometry, microstructure, and preparation of various types of uranium dioxide powders, as well as the initial cold-pressed density, will be factored into these studies.

Rod and flat-plate configurations will be utilized in determination of the relationship of bonding parameters and effects of uranium dioxide powder properties on the density and characteristics of gas-pressure-bonded uranium dioxide bodies. These fabricated components will be evaluated to determine fuel density, fuel properties, high-temperature stability, and integrity of cladding and bonds.

FF-2

The various types of uranium dioxide powders to be used in the initial program have been selected and are being procured. Determination of the cold-compacting characteristics of various UO_2 powders and the effects of the cold-pressed density on the final pressure-bonded density are being studied.

DEVELOPMENT OF URANIUM CARBIDE-TYPE
FUEL MATERIALS

F. A. Rough and W. Chubb

As a part of the AEC Fuel-Cycle Development Program, Battelle has undertaken a program of research to develop the technology of uranium carbides and UC-type fuel materials. By development of these new fuels it is expected that significant fuel-cycle economies may ultimately be accomplished.

Minor efforts of research have been carried out over many years on various aspects of uranium carbide technology, but until recently no sustained effort has been directed toward utilization of bulk uranium carbides as fuels. Recently, studies of bulk uranium carbides have been conducted in this country and in England, France, and Germany; however, only a start has been made thus far. In all of this research only a few samples of bulk uranium carbide have been irradiated.

Currently, Battelle in cooperation with Atomics International on another program is studying the effects of irradiation upon uranium carbide containing about 5.0 w/o carbon with encouraging results. This material was prepared by an arc-casting process. While too little information is available as yet to evaluate cast UC as a fuel material, these studies have stimulated increased interest in cast refractory fuels.

It is expected that the study of bulk carbides prepared by arc-casting will be emphasized in the fuel-cycle research now being conducted at Battelle; however, study of methods of preparing bulk uranium carbide by other processes is also being considered. For purposes of study the program is divided into five parts as outlined below.

- (1) Development of the arc-casting process for preparation of scaled-up bulk carbide or carbide-type samples of controlled size and quality will be undertaken.
- (2) Methods other than casting for preparing bulk uranium carbides will be evaluated. In this research the emphasis will be upon high-density products, although some study of materials having controlled porosity may be desirable.
- (3) The various physical characteristics and properties of the fuel materials developed in the above parts of the program will be investigated.

FF-3

- (4) Research to determine the rates and modes of diffusion of uranium and carbon in UC will be conducted. This research is needed as background for various aspects of the technology of UC, including production processes, fuel-fabrication procedures, and release of fission products by diffusion.
- (5) The final portion of the program will be devoted to characterization of the mechanism of the important effects of irradiation in uranium monocarbide.

Initial reports are included this month on three of the five sections of this program. Preparation and plans for research are being made on the remaining two sections and reports will be initiated on them next month.

Fabrication of UC by Powder Processes

S. J. Paprocki, D. L. Keller, and D. E. Kizer

Techniques for the production of UC of 95 per cent of theoretical density or better by powder-metallurgy methods will be investigated. Evaluations of the UC will be made upon the basis of the economy of fabrication and the quality of the material produced.

Powder-metallurgy techniques for preparing UC powder and dense UC bodies which may be attractive economically include (1) the reaction of uranium with UC_2 and carbon powders, (2) the reaction of the oxides of uranium and carbon powders, and (3) the reaction of uranium and uranium hydride with methane gas. Each of these processes will be investigated.

Modification of a Sieverts apparatus for preparing UC powder by reacting uranium metal with methane has begun. This method of producing UC powder for sintering studies is attractive in that temperatures of only 650 to 700 C are required. In addition, a vacuum-sintering apparatus to be used in conjunction with a high-frequency induction furnace is being modified. This equipment will be used to determine the feasibility of producing dense cores by reacting and sintering mixtures of the oxides of uranium with carbon. Also, the equipment will find use in high-temperature sintering studies of compacted UC powders. In the meantime, tantalum and molybdenum vacuum furnaces will be used to begin sintering and reaction studies.

Uranium and uranium hydride powders are being prepared to study the reaction characteristics and sinterability of stoichiometric mixtures with carbon. In addition, cores of UO_3 and graphite have been prepared for reaction studies. As materials become available, this study will include reactions of U_3O_8 as well as UO_2 with carbon to form UC.

Physical Characteristics and Properties
of Uranium Carbides

W. M. Phillips, E. L. Foster, and
R. F. Dickerson

One portion of a program for the development of UC and UC-type materials as power-reactor fuels is concerned with the determination of the effects of compositional variations on the qualities of materials of near-UC composition. In this research, cast specimens of UC containing 4.5 to 5.5 w/o carbon and other additions will be examined for their mechanical and chemical qualities.

The mechanical qualities of the cast specimens will be evaluated by bend tests, resistivity measurements, hardness measurements (before and after heat treatment), and density tests, as well as by observations made during radiographic, metallographic, and visual examinations. The chemical properties of cast specimens, as exhibited by their corrosion resistance in moist air at 40 C, water at 60 C, terphenyl at 400 C, and NaK at 600 C will be noted.

Additions to the UC-base material fall into two categories: (1) those that may be unintentionally or unavoidably present in starting materials or picked up during production of fuel material, and (2) intentional additives that impart some beneficial quality to the product. The impurities that might result from processing are being examined first. This work has been initiated and 33 arc-melted buttons containing the following nominal impurity additions have been prepared:

Additive	Nominal Addition to UC Material With Indicated Carbon Content, ppm	
	4.8 w/o Carbon	5.0 w/o Carbon
Iron	100, 300, 800	100, 300, 800
Silicon	100, 300, 800	100, 300, 800
Tungsten	100, 300, 800	100, 300, 800
Nitrogen	100, 200, 500	100, 200, 500
Oxygen	100, 200, 500	100, 200, 500

Additional buttons made from high-purity uranium and carbon have been prepared as control specimens. In preparing one button, the usual inert atmosphere was intentionally contaminated with hydrogen. The arc-melted buttons will be cast to cylindrical-shaped specimens and subjected to the examinations noted. Additional series of specimens at different carbon and impurity levels are planned.

Uranium Monocarbide Diffusion Studies

W. Chubb and F. A. Rough

In order to provide basic information on the nature of the uranium-carbon compounds and on their behavior at very high temperatures, a program has been initiated to determine the rates of diffusion of carbon and uranium in uranium-carbon alloys near

FF-5 and FF-6

the composition of uranium monocarbide. It is expected that tracer techniques will be required to determine self-diffusion rates below about 2000 C; no extensive regions of solid solubility exist in this system below 2000 C. The major objective of this program will be to determine these self-diffusion coefficients at temperatures below 2000 C. However, as an aid to the design of these self-diffusion experiments, interdiffusion rates in the range from 2000 to 2400 C will be determined on the uranium monocarbide-dicarbide solid solution.

During the last month a method of determining interdiffusion rates at 2000 to 2400 C was investigated. This method involves melting of carbon-saturated uranium in heavy-walled graphite crucibles and measuring the thickness of carbide formed. Three melts have been completed. At 1300 C and 1600 C the carbide layer was too thin to be visible to the naked eye. At 2000 C a carbide layer approximately 0.046 in. thick was formed in 2 hr. Several additional melts will have to be made and analyzed metallographically and perhaps chemically before diffusion coefficients can be calculated.

On the basis of these results, self-diffusion couples will be prepared using enriched uranium and carbon-14 as tracers. A suitable technique for using carbon-14 as a tracer in uranium monocarbide has not yet been devised.

G-1 and G-2

G. FATIGUE STUDIES OF INCONEL AND INOR-8

R. G. Carlson

Fatigue Studies of Inconel

The objectives of this program are to obtain basic fatigue information on Inconel and to establish quantitative relationships for Inconel among the variables of temperature, stress, strain, time, and cyclic frequency. The current phase of the program is concerned with measuring and recording strain in Inconel specimens under elevated-temperature fully alternating stress-cycling conditions.

During April, the planned stress-cycling tests were concluded. The data obtained for the three conditions studied will now be evaluated. These conditions were as follows:

- (1) At 60 cpm, 1500 F
- (2) At 60 cpm, 1300 F
- (3) At 6 cpm, 1500 F.

During May, the analysis of the data will be carried out and preparation of a topical report will be started.

Fatigue Studies of INOR-8

This program is concerned with the investigation of the temperature and frequency dependence of fatigue properties of INOR-8 alloy.

During April, rotating-beam tests of INOR-8 were completed for the 1300 F 100- and 3,000-rpm conditions. In addition, a study of the 1500 F 600-rpm condition was started.

During May, further tests will be carried out for the 1500 F 600-rpm condition. In addition, supplementary data will be obtained where needed for the other conditions studied. Specimens will be cycled at 100 and 3,000 rpm at 1100, 1300, and 1500 F.

H-1

H. PHYSICAL RESEARCH

F. A. Rough

The AEC Division of Research supports a series of four physical research projects, two of which are reported this month. Next month the progress on the other two projects will be reported.

Study of the niobium-nitrogen reactions has continued with emphasis on study of diffusion and evaluation of terminal solubilities of nitrogen in niobium. In the range of 800 to 1600 C the diffusion of nitrogen is represented by the equation $D = 0.0605 \exp(-38,800/RT)$.

In the study of uranium-niobium constitution the important characteristics of the system are being re-evaluated. Present studies in the vicinity of the gamma-phase immiscibility region are being conducted on diffusion samples of high purity by means of the electron-beam microprobe analyzer.

Niobium-Gas Reactions

W. M. Albrecht and W. D. Goode

A fundamental study is being made of the kinetics and mechanisms of the reaction of nitrogen with niobium. The study presently includes study of diffusion coefficients and terminal solubilities of nitrogen in niobium.

Reaction rates of niobium with nitrogen at atmospheric pressure in the range 700 to 1500 C have been reported. In additional experiments made at 1100 and 1600 C, the reactions followed a parabolic rate law with rate constants of 1.0×10^2 and 1.6×10^4 ($\mu\text{g}/\text{cm}^2$)²/sec, respectively. These values are in line with those reported over the temperature range 1200 to 1500 C. Reactions carried out at 900 C at pressures of 1/4 and 1/2 atm of nitrogen pressure had parabolic rate constants of 0.76 and 0.74 ($\mu\text{g}/\text{cm}^2$)²/sec, respectively. These are in good agreement with the rate constant of 0.69 ($\mu\text{g}/\text{cm}^2$)²/sec determined at 900 C and 1 atm of nitrogen pressure. It appears that the reaction of nitrogen with niobium at 900 C is essentially independent of pressure at 1/4 to 1 atm.

X-ray studies have been made on samples reacted with nitrogen at 800 to 1400 C. Both Nb₂N and NbN were found as reaction products up to and including 1000 C. Cubic and hexagonal NbN was found above 1000 C. The change in reaction products at about 1000 C is probably associated with the change in the reaction mechanism that has been previously reported.

Additional experiments have been made to measure the diffusion rates of nitrogen in niobium. Diffusion coefficients of 8.8×10^{-7} and 1.5×10^{-6} cm² per sec have been obtained at 1500 and 1600 C, respectively. The variation of diffusion coefficients with temperature over the range 800 to 1600 C has been determined by the least-squares method to be

H-2

$$D = 0.0605 \exp (-38,800/RT) , \quad (H-1)$$

where the activation energy is 38.8 ± 0.7 kcal per mole. This is in good agreement with the equation

$$D = 0.098 \exp (-38,600/RT) \quad (H-2)$$

published by Ang* for diffusion coefficients for nitrogen in niobium as determined by internal-friction studies. The relationship

$$D = 0.0072 \exp (-34,800/RT) \quad (H-3)$$

reported by Powers and Doyle** from internal-friction studies is in fair agreement with those of Ang and this work.

Terminal solubilities of 3.4 and 4.7 a/o nitrogen in niobium were obtained at 1500 and 1600 C, respectively, from the diffusion experiments. These terminal solubilities are being checked by metallographic examination of structures resulting from direct saturation of niobium with nitrogen.

An investigation of the reaction kinetics and products is being continued in the temperature range 900 to 1100 C to establish more definitely where the change in the parabolic rate mechanism occurs. The metallographic investigation of terminal solubilities of nitrogen in niobium is being continued.

Constitution of Uranium-Niobium Alloys

S. G. Epstein, A. A. Bauer, and R. F. Dickerson

The constitution of uranium-niobium alloys is being investigated by means of diffusion couples to establish the composition limits of the gamma-phase immiscibility gap in the system. The data obtained from the diffusion-couple analyses are also being used in the determination of diffusion coefficients at several temperatures. The studies are being performed with high-purity uranium and niobium and are intended to serve as a basis for future studies of the effects of impurities on uranium-niobium alloy constitution.

The electron-probe microanalyzer data for the diffusion couple heat treated at 1000 C for 50 hr have been analyzed by a method presented by Baroody***, which is an application of the Matano-Boltzmann method and which differs from the graphical method previously used for these data. In this method, a curve is obtained by plotting a function of concentration against position. This curve is approximated by a polynomial, and the diffusion coefficients are calculated from the coefficients of the polynomial. In application, the best fit for the data at 1000 C was found to be two straight lines intersecting approximately at the Matano interface. Two diffusion coefficients

*Ang, C. Y., Acta Metallurgica, 1, 123 (1953).

**Powers, R. W., and Doyle, M. V., Trans. AIME, 9, 1285 (1957).

***Baroody, E. M., J. Metals, p 819 (July, 1957).

H-3 and H-4

were then determined as 1.3×10^{-12} cm² per sec for concentrations between about 10 and 85 a/o uranium, and 45×10^{-12} cm² per sec for concentrations between about 85 and 95 a/o uranium. The change between these two values appears to be very abrupt. Agreement with the values obtained by the graphical solution is fairly good for concentrations up to about 70 a/o uranium. The values for higher uranium concentrations as determined by the graphical solution are much lower than the value of 45×10^{-12} cm² per sec. However, Adda* claims that the electron microprobe is essentially useless for the determination of diffusion coefficients of very dilute solutions, and a method such as autoradiography should be employed.

The diffusion couple originally heat treated at 925 C for 170 hr has been reheated to 925 C and further annealed for a total of 500 hr at temperature. Analyses are now being performed and additional data will be obtained shortly.

---

*Adda, Y., et al., AEC-TR-3503.

I-1

I. SOLID HOMOGENEOUS FUELED REACTORS

W. H. Goldthwaite

Research in support of the development and evaluation of spherical fuel elements for the Pebble-Bed Reactor program is reported in this section. For several months, this research has been directed at investigating the fission-product-retention characteristics of several types of graphite spheres (1-1/2 in. in diameter) fueled with uranium oxide and carbides. Fission gases released from specimens (1) during post-irradiation heat treatment following low-level irradiation (neutron activation) and (2) during high-temperature irradiations in the BRR core are collected on charcoal traps and measured by gamma-ray spectrometry. Data so obtained are indicative of the fission-product-retention characteristics of the spheres.

Fission-Product Release During Postirradiation Heating
of Uranium Oxide/Carbide-Graphite Spheres

R. Lieberman, P. Gluck, D. N. Sunderman, and M. Pobereskin

Evaluation of uranium-containing spheres by measurement of postirradiation fission gas release at elevated temperatures was continued in April.

A lumped, uncoated sphere containing UC_2 was irradiated for 2 min at a thermal-neutron flux of 9.74×10^{11} nv. Nineteen days after irradiation the specimen was placed in a preheated furnace and heated at two temperatures. The fission gas which was released was adsorbed on activated charcoal. Helium, flowing at 3 liters per hr, was used as a carrier gas. The fission gas released was measured by radioassay of individual traps for xenon-133 by means of gamma-ray spectrometry. The activity in the last five of the seven samples at 1000 F and at 1500 F was below the minimum detectable limit of 0.05 per cent of that present. The data from this experiment are shown in Table I-1.

An admixture uncoated sphere containing UC_2 was irradiated for 4 min at a flux of 6.0×10^{11} nv. Twelve days after irradiation the specimen was heated at two temperatures using the same procedure and cycle described in the previous experiment. The results of this experiment are shown in Table I-2.

During the month of April the SiC-silicon-coated lumped UC_2 -graphite sphere was reirradiated for 15 min at a flux of 6.9×10^{11} nv. Four days after irradiation, the specimen was heated at 1500 F. No xenon-133 was detected in any of the sample tubes obtained under the same sample schedule as shown in Table I-1. The minimum identification limit for this experiment was calculated to be 0.001 per cent of the xenon-133 present.

An admixture UC_2 -graphite sphere coated with silicon carbide was irradiated for 2 min at a flux of 9.7×10^{11} nv. This specimen was heated at 1000 F and 1500 F. With a minimum identification limit of 0.03 per cent, no xenon-133 was found in any of the charcoal traps.

TABLE I-1. FISSION GAS RELEASE FROM A LUMPED UC_2 -GRAPHITE SPHERE AS A FUNCTION OF TIME AND TEMPERATURE OF POSTIRRADIATION HEAT TREATMENT

Time at Temperature, min	Temperature Change During Time, F	Fraction of Total Present Xenon-133 Found ^(a)
<u>Heated at 1000 F</u>		
10	<100 to 1000	.0087
20	At 1000	.0087
40	At 1000	.0093
60	At 1000	.0093
120	At 1000	.0093
240	At 1000	.0093
360	At 1000	.0093
<u>Heated at 1500 F</u>		
10	<100 to 1500	.0008
20	At 1500	.0010
40	At 1500	.0010
60	At 1500	.0010
120	At 1500	.0010
240	At 1500	.0010
360	At 1500	.0010

(a) Cumulative value for time at temperature.

TABLE I-2. FISSION GAS RELEASE FROM ADMIXTURE UC_2 -GRAPHITE SPHERE AS A FUNCTION OF TIME AND TEMPERATURE OF POSTIRRADIATION HEAT TREATMENT

Time at Temperature, min	Temperature Change During Time, F	Fraction of Total Present Xenon-133 Found ^(a)
<u>Heated at 1000 F</u>		
10	<100 to 1000	.0066
20	At 1000	.0074
40	At 1000	.0075
60	At 1000	.0077
120	At 1000	.0080
240	At 1000	.0088
360	At 1000	.0095
<u>Heated at 1500 F</u>		
10	<100 to 1500	.0014
20	At 1500	.0030
40	At 1500	.0042
60	At 1500	.0048
120	At 1500	.0056
240	At 1500	.0067
360	At 1500	.0076

(a) Cumulative value for time at temperature.

Fission-Product Release During Irradiation
of Uranium Oxide/Carbide-Graphite Spheres

G. E. Raines and W. H. Goldthwaite

During April the in-pile capsule for the second sweep-gas experiment was completed. This capsule contains two pairs of coated uranium carbide-bearing spheres. It is anticipated that the irradiation of this capsule will be initiated in May.

One pair of specimens is coated with a 1 to 3-mil layer of siliconized silicon carbide (SiC-silicon), the other with approximately a 1/32-in. thickness of silicon carbide. Specimens selected for the irradiation have shown no porosity by a test in which the specimens are immersed in a silicone-oil bath at 375 F. The presence of porosity is indicated by bubbles as the gases entrapped in the specimen emanate.

It was originally supposed that the coatings on all specimens were free of fuel; however, as some information concerning manufacturing techniques became available, it was apparent that the SiC-coated balls could have fuel near the surface because of a high temperature during a phase of the fabrication. Alpha-particle counting was used to detect the presence of uranium near the surface of nine of these specimens (the actual specimens employed in the capsule were not counted as they were already encapsulated). Two of the SiC-silicon-coated specimens, in which no surface contamination was expected, were also checked with resulting count rates of 120 and 135 per min. The rates for the nine SiC-coated specimens varied from 25,500 to 140,000 counts per min with an arithmetic average of 63,900. The rates mentioned above have been corrected for counting efficiency. Any uranium which is near enough to the surface of the specimen to allow the fission products to enter the sweep-gas stream by recoil will provide a source of radioactivity in addition to that which diffuses through or leaks through the coating.

J-1

J. PROBLEMS ASSOCIATED WITH THE RECOVERY OF SPENT REACTOR FUEL ELEMENTS

CORROSION STUDIES

C. L. Peterson, P. D. Miller, O. M. Stewart, J. D. Jackson,
W. N. Stiegelmeier, W. C. Baytos, T. E. Snoddy, and F. W. Fink

The evaluation of materials of construction for the Darex, Sulfex-Thorex, Darex-Thorex, Zirflex, and Fluoride-Volatility processes for the recovery of spent nuclear-reactor fuel elements is being conducted as a program of assistance to the Chemical Technology Division at ORNL.

The accumulated data indicate that the use of Type 304 ELC stainless steel piping cannot be recommended for transferring Darex dissolver solutions. Dissolution of fuel pins in a Ni-o-nel dissolver by the Sulfex-Thorex process has not produced serious attack of the vessel during a relatively short exposure. Only nine pins have been dissolved because of difficulties arising from passivation of the cladding and incomplete core dissolution. Less difficulty has been experienced with a Titanium 75A dissolver in which 15 pins have been dissolved by the Darex-Thorex route. Corrosion of this dissolver has been limited to a slight etch around weldments in the vapor phase. Significantly lower corrosion rates were measured for INOR-8 specimens exposed to molten NaF-LiF salt, while dissolving Zircaloy-2 under hydrofluorination conditions, than had occurred on previous comparable runs without dissolution.

The Darex Process

Dilute aqua regia is used to dissolve stainless-clad or -bearing fuel elements in the Darex process. After removal of the chloride and adjustment of the solution, uranium is recovered by solvent extraction.

The final studies with titanium, the material of choice for use in corrosive areas of this process, were summarized in BMI-1330. No further work with titanium has been done.

It was hoped that existing Type 304 ELC stainless steel pipelines at ORNL could be used to transfer Darex solutions following the dissolution of APPR elements to other locations for adjustment operations. Experiments conducted at BMI, however, indicate that this would not be advisable. It was found that a borderline condition of activity-passivity for Type 304 ELC existed in these solutions. Catastrophic attack occurred on some specimens, while others remained virtually unattacked at temperatures as low as 105 F.

The Sulfex-Thorex Process

In the combined Sulfex-Thorex route, stainless-clad fuel elements of thoria are to be dejacketed with boiling 6 M H_2SO_4 . After washing, core dissolution is accomplished with a boiling 13 M HNO_3 , 0.04 M F^- solution containing sufficient aluminum to mitigate corrosion.

Experiments With Ni-o-nel

Ni-o-nel specimens have been exposed for several hundred hours to boiling 3.5 M H_2SO_4 solutions containing the equivalent of 50 g per liter of dissolved Type 304 stainless steel. The stainless addition was made in two ways: (1) by addition of Fe^{++} , Cr^{+6} , and Ni^{++} salts, and (2) by dissolution of Type 304 stainless steel rod. After an initial period of higher rates in the latter solutions, corrosion rates became similar in the two solutions, being about 0.4 mil per month for liquid exposure after 480 hr. Intergranular attack is somewhat more pronounced on specimens exposed to Solution 1. Exposure of these specimens is being continued.

Bench Dissolution of Fuel Pins by the Sulfex-Thorex Process

Consolidated Edison fuel pins are being dissolved in a bench-scale Ni-o-nel dissolver by a Sulfex-Thorex route. The dissolver, of welded construction, was heat treated for 2.0 hr at 1950 F and air quenched. Weldments were also made in the dissolver after heat treatment. One fuel pin is dissolved at a time using a schedule of 3 hr in boiling 6 M H_2SO_4 , water rinse, 5 hr in a boiling solution of 13 M HNO_3 , 0.04 M F^- , and 0.04 M Al^{+3} , followed by a second pass of 3 hr with fresh solution of the same composition, and a final water wash.

Nine of a scheduled 25 pins have been dissolved. On several occasions, difficulties with passivation of the pins during decladding have been encountered. In addition, the core-dissolution step has been ineffective several times. This seems to be a result of carryover of stainless steel sulfates into the Thorex solutions. Ni-o-nel coupons exposed in the dissolver show corrosion rates in the neighborhood of 2 mils per month. Incipient intergranular attack can be observed, especially in the heat-affected area of the weldments made after heat treatment. In general, the appearance of the dissolver, following this limited exposure to the solutions, is good. Changes in operating techniques are expected to minimize the passivation difficulties and dissolution of the pins will be continued.

The Darex-Thorex Process

If titanium, which has already been shown to be the material of choice for the Darex Process, will withstand the Thorex solutions, a combined Darex-decladding Thorex-core-dissolution process would be attractive.

J-3

Scouting Experiments With Titanium

Over 750 hr of exposure of welded titanium specimens to Thorex core-dissolution solutions has been completed. The greatest attack occurs on specimens exposed in the vapor phase. With no additions of thorium or aluminum, this amounts to 8 mils per month. Addition of 0.04 M Th^{+4} decreases this rate only slightly in the vapor but does lower the corrosion in the liquid phase. Aluminum additions lower the rates in the vapor to 2 to 3 mils per month and the rates in the liquid to less than 0.5 mil per month. In the absence of any additions, a uniform attack occurs which leaves the surfaces smooth and shiny. A small addition of aluminum (0.04 M) results in a black coating on the specimens with very little localized attack. However, as the aluminum addition is increased through 0.09 and 0.15 to 0.20 M, the attack on specimens exposed in the vapor phase becomes more localized, with pitting appearing at 0.09 M. This changes to intergranular attack in the heat-affected areas and finally to incipient knife-line attack by the time 0.20 M is reached. This attack has not reached serious proportions by the end of 756 hr of exposure. However, it appears that, as more fluoride is complexed and removed from the vapor phase, the attack becomes more localized, indicating that, since the solution becomes less corrosive as it builds up in thorium, it might be desirable to accept the higher rate of the general attack in the absence of aluminum in order to minimize the over-all corrosion. This point remains to be investigated.

Bench Dissolution of Fuel Pins by the Darex-Thorex Process

Consolidated Edison fuel pins are also being dissolved in a bench-scale dissolver constructed from Titanium 75A. Again, dissolution of 25 pins is scheduled in this as-welded vessel. Fifteen pins have been dissolved with very little difficulty using a Darex-Thorex process. There is some evidence of etching around the weldments in the vapor phase of the container. Titanium coupons immersed in the liquid phase show slight gains in weight, while coupons in the vapor phase show only about 0.2-mil per month penetration. These vapor-phase coupons have been exposed for only 53 of the total accumulated 126 hr. The decladding is accomplished in 1 hr using 500 ml of 2 M HCl, 5 M HNO_3 per pin. The core dissolution follows the same schedule described for the Ni-o-nel dissolver.

The Zirflex Process

No new studies concerning the Zirflex process were conducted this month, nor are any more planned during the present contract period.

The Fluoride-Volatility Process

Uranium fuel elements, clad with zirconium or Zircaloy-2, can be hydro-fluorinated in a molten-salt bath sparged with HF. Following this step, the uranium

is converted to the volatile UF_6 by sparging the same bath with fluorine or a fluorinating agent. INOR-8 has been evaluated as a material of construction for the hydrofluorinator.

The specimens from the latest run in the NaF-LiF salt in which dissolution of Zircaloy-2 was carried out, as described in BMI-1330, have been examined. The over-all penetrations obtained in this experiment were significantly lower than those from comparable runs made in the absence of dissolving Zircaloy-2. In earlier runs in this same salt, the specimens were often severed at the liquid-vapor interface. Very little interface attack was noted in this last run, except at one area on an INOR-8 thermocouple well where about 9 mils of metal was removed (31 mils per month). Also, some thinning (7 to 23 mils per month, depending on the dimension measured) occurred at the interface zone of one INOR-8 coupon which was raised throughout the experiment to maintain a constant interface position. Considerably less attack occurred on tubes and coupons which remained stationary while the salt level rose. No serious attack occurred on a submerged specimen, which included a lap weld and a crevice.

This dissolution experiment has demonstrated the effectiveness of dissolving metal in retarding the corrosion of container materials. The reason for the inhibition is not clear, as the lower corrosion rates occurred both on electrically insulated and connected coupons. Hence, they could not be ascribed entirely to cathodic protection. No further evaluations of hydrofluorinator materials are planned during the present contract period.

A corrosion study of specimens from the ORNL pilot-plant fluorinator and its auxiliary equipment is under way. The types of attack are being determined and the extent of penetration is being measured by metallographic methods.

STUDY OF THE EFFECT OF IRRADIATION
ON CLADDING- AND CORE-
DISSOLUTION PROCESSES

R. A. Ewing, D. K. Dieterly, and M. Pobereskin

Preparatory work is proceeding on the investigation to determine the effects of irradiation on decladding and core dissolution of Consolidated Edison fuel pins by the Sulfex process.

The all-glass dissolution equipment is currently being fabricated. Although this has been delayed by slow deliveries of purchased components, it is expected that fabrication can be completed next month. A number of analytical procedures needed for the Sulfex-process study have been checked out during April, using both simulated process solutions and actual ones resulting from the corrosion studies currently being conducted by another group at Battelle.

J-5 and J-6

Six normal, unirradiated 7-in. Consolidated Edison pins have been received from ORNL. It is expected that preliminary "cold" runs with these pins can be initiated during May.

K-1

K. DEVELOPMENTS FOR SRE, OMRE, AND OMR

EVALUATION OF URANIUM MONOCARBIDE AS A REACTOR FUEL

F. A. Rough

Evaluation of the effects of irradiation on a series of arc-cast uranium carbide samples is being performed. Various data have already been reported on 5.0 w/o carbon samples irradiated up to about 6400 MWD/T. This month the principal data are those based on metallographic observations of samples irradiated to 4400 and 6400 MWD/T. Two additional capsules of 5.0 w/o carbon specimens are currently being irradiated to burnups of 10,000 and 15,000 MWD/T and two capsules containing 4.6 and 4.8 w/o carbon specimens are awaiting irradiation.

Irradiation of Uranium Monocarbide

D. Stahl and W. H. Goldthwaite

The irradiation of Capsules BMI-23-3 and BMI-23-4, containing uranium monocarbide (5.0 w/o carbon) specimens, is continuing in the A-28-NE and A-27-SE positions, respectively, of the MTR. During Cycles 119 and 120, Capsule BMI-23-4 operated with a fairly stable top-specimen core temperature of about 1190 F. Capsule BMI-23-3, on the other hand, operated during Cycle 119 with a central core temperature ranging between 1300 and 1400 F; however, during Cycle 120, the central core temperature range for BMI-23-3 was 1200 to 1260 F. This temperature will be watched closely during Cycle 121. If it remains low, a request to lower the capsule during shutdown for Cycle 122 will be made in order to obtain a somewhat higher flux and higher temperature.

The irradiation of Capsule BMI-23-4 has been changed from 9 cycles to 18 cycles (to a total burnup of 15,000 MWD/T). The schedule for BMI-23-3 is unchanged; it is to be in-pile 12 cycles (to a burnup of 10,000 MWD/T). Discharge dates on this basis are September 21 for BMI-23-3 and December 14 for BMI-23-4. Because of this extension, reactor space is now being sought for the insertion of Capsules BMI-23-5 and BMI-23-6 (containing 4.6 and 4.8 w/o carbon, respectively). Originally, these were scheduled to follow BMI-23-3 and BMI-23-4.

Burnup calculations were made using the results of the radiochemical analyses of dosimeter wires taken from Capsule BMI-23-2. These indicate nominal burnups of 4400 and 6400 MWD/T for the top and bottom 2-in. specimens, respectively. These are in good agreement with values of 4600 and 5700 MWD/T obtained by using reactor-quoted fluxes and a perturbation factor based on the Brad Lewis empirical correlation. The target burnup for specimens in this capsule was 5000 MWD/T.

K-2

Postirradiation Examination of Uranium Monocarbide

S. Alfant, A. W. Hare, and F. A. Rough

Three capsules containing uranium monocarbide specimens have been irradiated and returned to BMI for examination. Data compiled after examination of one capsule irradiated at the BRR and of one capsule (Capsule BMI-23-1) irradiated for one cycle at the MTR indicated that irradiation produced no severe effects on the dimensional stability of UC.

Two irradiated uranium monocarbide specimens taken from Capsule BMI-23-2 were examined and the results were compared with data obtained on these specimens prior to irradiation. The top specimen in the capsule experienced an estimated burnup of 4400 MWD/T based on dosimetry, and mean core and surface temperatures were 1375 and 915 F, respectively. The bottom specimen experienced an estimated burnup of 6400 MWD/T based on dosimetry, and mean core and surface temperatures were 1112 and 700 F, respectively. The postirradiation dimensional measurements reported last month indicated that the UC appeared to behave very well at the temperatures and burnup levels experienced in this capsule (a 0.9 per cent diameter increase was observed as a result of irradiation).

However, during the past month metallographic examinations of both specimens were completed. The results of these examinations indicated that the effects of irradiation were more severe than on the specimens taken from Capsule BMI-23-1 and the BRR capsule. There was general cracking in the areas where the temperature was highest, especially near the thermocouple, which operated as high as 1830 F in the center of the top specimen. Examination of the areas surrounding the thermocouple hole in the top specimen indicated the existence of large voids and cracks. The cracking, in most instances, extended to the surface of the specimen. The bottom specimen also seemed to have its highest concentration of voids and cracks in the center. It appears unlikely that the high concentration of voids could be entirely caused by fission-gas bubbles. Because of the large volume of voids at the point of highest temperature near the center thermocouple, it is highly probable that the voids were caused by corrosion by the NaK. Unfortunately, no compatibility data are available for UC, NaK, and stainless steel at 1830 F to confirm this.

Some difficulties are being encountered in determining burnup by radiochemical analysis, although considerable work has been done to develop and calibrate procedures for determining burnup in UC and graphite matrix materials by analysis for cesium-137. Additional details will be furnished.

Preparation of UC Pins for Irradiation in the SRE

E. L. Foster and R. F. Dickerson

Specific techniques for the preparation of cast specimens of UC 0.6 in. in diameter have been established, as reported last month. The actual preparation and pre-irradiation examination of pins for irradiation at the SRE will begin as soon as the enriched uranium is received.

L-1

L. TANTALUM AND TANTALUM-ALLOY STUDIES

J. H. Stang

After careful metallurgical screening, a group of tantalum-base-alloy specimens was sent to Los Alamos Scientific Laboratory during April for compatibility experiments with plutonium-base fuels. Alloying agents were carbon, rhenium, and yttrium. In the case of the carbon and rhenium alloys, there is a marked tendency toward grain refinement; however, the former with additions above 0.025 w/o are brittle inasmuch as grain-boundary precipitation is excessive.

The second program reported here is concerned with determining irradiation-damage effects in tantalum. Two irradiation capsules containing tantalum tensile bars have been shipped to MTR and, according to present schedule, will be inserted during May. Tantalum-tungsten alloy specimens are being prepared as controls for evaluation of tensile properties of unirradiated materials.

Development of Container Materials for LAMPRE Applications

D. C. Drennen, M. E. Langston, C. J. Slunder, and J. G. Dunleavy

The second series of 0.030-in. -thick tantalum-alloy strip specimens containing additions of either carbon, rhenium, or yttrium has been sent to LASL in the following three conditions for plutonium-alloy compatibility evaluation: (1) cold rolled, (2) annealed, and (3) homogenized at 4000 F, cold rolled, and annealed. Potassium ferrocyanide tests indicated that the specimens were free of surface iron contamination. Hardness, grain-size, and analytical data for these materials are presented in Tables L-1 and L-2. In all cases, the levels of gaseous and metallic contaminants of the materials were relatively low. There was, however, a very slight increase in the total content of gaseous interstitial elements during the vacuum-annealing treatment.

The chemical analyses showed that the recoveries of carbon and rhenium were very good whereas the yttrium additions were apparently lost during melting. However, the low recovery may be unimportant insofar as scavenging effects are concerned. This possibility will be investigated further.

It was observed that the addition of rhenium to tantalum had a refining effect upon the grain size of the annealed material. For example, the grain size of the annealed alloys containing 1.5 to 3 w/o rhenium was about half that of the annealed unalloyed tantalum specimen, while the grain size of the 6 w/o rhenium alloys was about one-third that of the unalloyed tantalum specimens and about one-half that of the 1.5 and 3 w/o rhenium alloys. The addition of carbon to tantalum appeared to have a similar refining influence on the grain size.

Room-temperature tensile properties have been determined on 0.030-in. -thick strip specimens of the tantalum-rhenium alloys in the annealed condition. The data in Table L-3 show that an increase in strength and a decrease in ductility result from increased additions of rhenium to tantalum. The yield and ultimate tensile strength of the

TABLE L-1. HARDNESS AND GRAIN SIZE OF BINARY TANTALUM-BASE ALLOYS

Parent Arc-Melted Button(a)	Nominal Composition (Balance Tantalum), w/o	Hardness of Strip, VHN			Average Grain Diameter of Strip, mm	
		As-Rolled	As-Annealed	Homogenized, Cold Rolled, and Annealed	As-Annealed	Homogenized, Cold Rolled, and Annealed
27L	Unalloyed	129.0	86-90(b)	--	0.100	--
28L	1.5 Re	238.5	144-155(c)	--	0.060	--
29L	1.5 Re	244.5	138(c)	--	0.050	--
30	3 Re	316.5	--	205(c)	--	0.036
31L	3 Re	290.0	203-211(c)	--	0.060	--
32L	6 Re	387.0	--	--	--	--
33L	6 Re	382.5	264-267(c)	--	0.036	--
35L	0.025 C	186.5	97(d)	93(b)	0.036	0.042
36	0.100 C	337.5	--	--	--	--
34	0.25 C	219.0	--	--	--	--
43	0.25 C	238.5	--	--	--	--
38L	0.025 Y	152.5	85(b)	--	0.060	--
39L	0.100 Y	125.0	80(c)	86(c)	(e)	(d)
37L	0.25 Y	203.0	114(c)	--	0.120(c)	--

(a) Specimens sent to Los Alamos were fabricated from buttons with designation followed by L.

(b) Annealed 2 hr at 2600 F.

(c) Annealed 1 hr at 2600 F and 1 hr at 2700 F.

(d) Annealed 1 hr at 2600 F.

(e) Grain size not determined because of nonequiaxed grains.

TABLE L-2. CHEMICAL ANALYSES OF COLD-ROLLED AND OF ANNEALED TANTALUM-CARBON, TANTALUM-RHENIUM, AND TANTALUM-YTTRIUM

0.030-In. Strip Specimens

Parent Arc-Melted Button	Composition (Balance Tantalum), w/o		Actual Composition, ppm													
	Nominal	Analyzed	C	H	N	O	Fe	Si	Cu	W	Nb	Zr	Al	Mo	Ni	Cr
<u>Cold Rolled^(a)</u>																
27L (control)	Unalloyed	--	20	1.0	30	28	3	10	2	100	50	10	5	10	3	1
28L	1.5 Re	1.50 Re	20	1.0	70	32	3	10	3	100	50	10	5	10	3	1
29L	1.5 Re	1.50 Re	20	0.5	30	15	10	10	5	100	50	10	5	10	3	1
30	3 Re	2.85 Re	40	1.5	50	24	3	30	10	100	50	10	5	10	5	1
31L	3 Re	2.75 Re	60	0.5	50	17	3	30	5	100	50	10	5	10	3	1
32L	6 Re	6.0 Re	50	2.5	10	25	3	30	5	100	50	10	5	10	3	2
33L	6 Re	6.2 Re	20	0.5	20	14	3	30	10	100	50	10	5	10	3	2
35L	0.025 C	0.031 C	--	1.0	20	16	3	10	10	100	50	10	5	10	3	2
38L	0.025 Y	<0.001 Y	10	1.5	20	22	3	10	20	100	50	10	5	10	3	2
39L	0.10 Y	<0.001 Y	10	1.0	10	16	3	20	5	100	50	10	5	10	3	2
37L	0.25 Y	<0.001 Y	20	3.0	70	18	3	10	5	100	50	10	10	10	3	2
<u>Vacuum Annealed^(b)</u>																
27L (control)	Unalloyed	--	10	0.5	30	37	3	10	3	100	50	10	5	10	3	1
28L	1.5 Re	1.50 Re	10	0.5	40	33	3	15	8	100	50	10	5	10	3	1
31L	3 Re	3.0 Re	30	0.5	30	23	3	20	15	100	50	10	5	10	3	1
33L	6 Re	5.5 Re	40	0.5	20	24	3	20	15	100	50	10	5	10	3	1
35L	0.025 C	0.028 C	--	0.5	40	20	3	10	3	100	50	10	5	10	3	1
38L	0.025 Y	<0.001 Y	10	0.5	50	23	3	10	5	100	50	10	5	10	3	1
39L	0.10 Y	<0.001 Y	30	0.5	30	9	3	10	30	100	50	10	5	10	3	1
37L	0.25 Y	<0.001 Y	10	0.5	80	25	3	10	3	100	50	10	5	10	3	1

(a) Reductions of 80 to 85 per cent after intermediate anneal.

(b) Specimens were vacuum annealed at 2600 to 2700 F for 1 to 2 hr.

TABLE L-3. ROOM-TEMPERATURE TENSILE PROPERTIES^(a) OF ANNEALED TANTALUM-RHENIUM ALLOYS

0.030-In. Strip Specimens Vacuum Annealed at 2600 F for 1 Hr

Parent Arc-Melted Button	Actual Composition (Balance Tantalum), w/o	0.2 Per Cent Offset Yield Strength, psi	Ultimate Tensile Strength, psi	Elongation in 1 In., per cent
29L	1.50 Re	43,400	57,200	26
30	2.85 Re	76,300	86,500	14
32L ^(b)	6.0 Re ^(b)	115,300	117,600	5

(a) Results are the average of triplicate specimens per composition.

(b) Not fully recrystallized.

L-5 and L-6

tantalum-3 w/o rhenium alloy was almost double that of the 1.5 w/o rhenium alloy, while the ductility was reduced about half. Examination of the tantalum-rhenium alloys showed that the 6 w/o rhenium alloy was not completely recrystallized. Therefore, the strength properties are probably higher and the elongation lower than would be expected in the case of material that was fully recrystallized.

The arc-melting of binary tantalum-base alloys containing minor additions of hafnium, thorium, titanium, zone-refined high-purity tungsten, and zirconium will be initiated during the early part of May. These alloys are being prepared to continue the study of the influence of scavenger elements on the corrosion resistance of tantalum in plutonium-base melts. In this study, considerable effort will be devoted to identification of contaminating phases which may contribute to susceptibility to attack.

Effect of Irradiation on Tantalum

J. A. DeMastry, F. R. Shober, and R. F. Dickerson

It is expected that exposure to the anticipated neutron flux of the LAMPRE will result in two modifications of tantalum: fast-neutron damage and conversion of tantalum to tungsten (approximately a tantalum-3 w/o tungsten alloy will be formed). In order to evaluate and separate the effects of alloying (transmutation) from the effect of fast-neutron damage (atom displacement), the tensile properties of irradiated tantalum and unirradiated tantalum-tungsten alloys will be compared.

Two capsules containing six sheet tantalum tensile specimens in an environment of NaK have been fabricated and shipped to the MTR; they are scheduled for insertion during May. The capsules are to be exposed to obtain approximately 7×10^{20} and 1.4×10^{21} nvt; these exposures are necessary for the transmutation of 1.5 and 3.0 w/o tantalum to tungsten. A core position of high thermal flux and low fast flux in the test reactor has been requested. Nickel-cobalt and pure nickel wire have been inserted in the capsules as dosimeters for determination of the thermal- and fast-neutron fluxes, respectively.

Tantalum-1.5 and -3.0 w/o tungsten alloys have been arc melted and will be rolled to sheet. Tensile specimens will be machined from this sheet and used for control experiments.

M-1

M. DEVELOPMENTAL STUDIES FOR THE PWR

R. W. Dayton

The studies concerned with the development of a plate-type oxide fuel element for the PWR have been continued. Techniques are being developed for the coating of UO_2 cores with graphite, carbon, and chromium to prevent reaction between the UO_2 cores and Zircaloy cladding. Specimens having cores coated by the various processes will be pressure bonded and evaluated.

Pressure Bonding of Zircaloy-2-Clad Fuel Elements
Containing Compartmented Oxide Fuel Plates

E. S. Hodge

A compartmented flat-plate Zircaloy-2-clad fuel element containing uranium dioxide cores is being considered for the PWR Core 2. The gas-pressure-bonding technique is being employed as a backup method of fabricating these compartmented fuel plates. In this technique, the fuel elements are assembled using belt-abraded strip components that are fusion edge welded to form an envelope which is evacuated, sealed, and pressure bonded at 1550 F for 4 hr using a helium gas pressure of 10,000 psi. In experiments with this bonding operation, reaction occurred between the cladding and core; consequently, it was necessary to develop a barrier layer to minimize or prevent this reaction. The most economical and also effective barrier layer was determined to be sprayed graphite. A number of specimens were pressure bonded and critically evaluated. Although many of these specimens were satisfactory in all tests, some of the specimens exhibited inconsistent and weak bonds at high burst pressures. Evaluation of these specimens tended to indicate that the graphite smeared onto the Zircaloy surfaces during assembly, causing weak bonds. A limited number of specimens were run in which the graphite-coated cores were buffed and very carefully assembled for bonding. These specimens did not display any weak bonds. A program is now being initiated to determine if sprayed graphite-coated cores which are buffed and carefully handled can be bonded with consistent results or if some other coating might be more desirable. The other coatings being investigated are crystalline carbon and chromium.

Coating of Uranium Dioxide Cores With
Pyrolytic Carbon

E. H. Layer

Techniques for the coating of uranium dioxide cores with pyrolytic carbon by the methane-cracking process are being investigated. This process is now used to produce very hard crystalline-carbon coatings on steatite and other ceramics. In this process,

the pieces to be coated are heated to 1830 F in an atmosphere containing methane. Cracking of methane at this temperature produces a hard, uniform coating of crystalline carbon on the surface of the pieces. The hydrogen produced in the operation is allowed to pass from the furnace.

A total of 120 cores have been coated with pyrolytic carbon. This coating is several microinches in thickness and is hard and adherent. The films can be consistently produced with proper control of the cracking atmospheres. It has been found that a more adherent coating is produced if the UO_2 cores are sandblasted prior to coating. With this precaution, a large number of cores have been coated in one operation with no evidence of the coating peeling after deposition.

Thicker films have been attempted; however, these coatings all flaked when the cores were cooled from the deposition temperature. More specimens will be coated at different conditions to determine if thicker coatings can be applied.

A study is being made of methods that can be used to accurately measure the coating thickness. A smear-and-scrape test will be used as a qualitative test of coating adherence.

Coating of Uranium Dioxide Cores by Vapor Deposition of Chromium

E. H. Layer

Chromium has been determined to be an effective barrier layer in preventing reaction between Zircaloy and uranium dioxide at bonding temperatures of 1500 to 1525 F. One of the promising methods of coating a large batch of cores in a one-step operation is vapor deposition. A program has been initiated to determine the feasibility of this process for chromium coating of uranium dioxide platelets.

Approximately 100 platelets have been coated by vapor deposition. Preliminary evaluations of these coatings are promising. Some of the cores were sandblasted prior to coating, and others were coated in the as-pressed condition. All of the coatings were adherent. A large number of specimens can be coated in one operation on all surfaces with the recent development of a rotating jig.

Chromium has been deposited on cores with a thickness of several microinches. The coatings are dense, uniform, and adherent, and show no evidence of peeling or flaking. The upper limit on thickness of coating has not been experimentally determined; however, preliminary results indicate that thicker coatings are feasible.

Resistance measurements made on chromium coatings from a batch operation indicate that the thickness of the films will vary and will depend upon the position of the core in the rotating jig. Other sources than the evaporation of chromium from a single tungsten boat will be studied in an attempt to obtain more consistent coating thicknesses.

M-3

Chromium Coating of UO_2 Cores

E. A. Beidler and J. M. Blocher, Jr.

Chromium was deposited on UO_2 cores by dipping the cores in liquid CrI_2 and reducing the film of iodide in a hydrogen atmosphere. Although the coatings obtained in the 1 to 10- μ range should be of interest as diffusion barriers, the condition of deposition will be further explored in an effort to improve the uniformity and adherence of the coatings before specimens are submitted for pressure-bonding tests.

Pressure-Bonding Studies

S. J. Paprocki, E. S. Hodge, D. C. Carmichael,
and P. J. Gripshover

Fabrication of Zircaloy-2-clad uranium dioxide compartmented fuel plates by pressure bonding is being further investigated. In previous studies, it was determined that pressure-bonded fuel plates can be produced with consistent Zircaloy-to-Zircaloy bonds using buffed coatings of sprayed-on graphite on oxide cores when care is taken in the handling of the fuel plates prior to bonding. However, because graphite smears easily, other types of coatings would be desirable. Coatings of crystalline carbon and chromium are also being investigated. The effect of these coatings on the pressure bonding of clad fuel plates will be determined. A number of fuel plates embodying cores coated with buffed graphite will also be bonded and evaluated.

The effect of internal void space and chipped cores on the final dimensions of the fuel plates after pressure bonding is being investigated. The excessive flow required to fill internal void space may severely thin the cladding or remove the barrier layer from the core. The former could result in cladding rupture and the latter in a core-cladding reaction if the void space were sufficiently large. This study will determine the upper limit on tolerable void space.

The Zircaloy cladding components have been fabricated for the series of gas-pressure-bonded elements being prepared to permit evaluation of the core coatings and the effects of measured amounts of intentional internal void space. These elements are approximately 3.5 in. wide and 8 in. long with a thickness of 0.150 in. consisting of a 0.100-in.-thick receptacle plate and two 0.025-in.-thick cladding plates. Each element contains 32 uranium dioxide cores with dimensions of 0.100 by 0.250 by 1.500 in. The cores are separated into 32 individual compartments by 0.035-in.-wide Zircaloy ribs. The compartmented receptacle plate is assembled entirely from belt-abraded strip components. A longitudinal Zircaloy strip placed in the center of the element permits the element to be easily sectioned into two portions after bonding. One of these halves is evaluated in the as-bonded condition and the other is evaluated after an additional 1850 F heat treatment.

M-4

These elements will be prepared in sets of three elements for each coating technique. One of the three elements in each set will be prepared with the minimum possible internal void space, the second will contain various measured amounts of void space at the end of each longitudinal row of compartmented cores, and the third will contain cores which have had various measured amount of material ground from one corner to simulate chipped cores. Most of the elements are to be prepared by the edge-welding technique; however, one or two sets of elements are to be assembled into protective stainless steel containers with Ti-Namel spacers and intermediate graphite-coated stainless steel barrier plates between the elements and the Ti-Namel spacers. It is desired to determine if an element bonded in a container with spacers is subjected to less severe flow of the cladding plates into the internal void spaces.

Six edge-welded elements have been pressure bonded in the current series. One set of three elements contained sprayed-graphite-coated cores which were buffed, and the other set of three contained cores coated with crystalline carbon by the methane-cracking technique. These elements were fusion edge welded in a helium-atmosphere tank, evacuated, sealed, and pressure bonded at 1500 F and 10,000 psi for 4 hr. Half of each element was heat treated for 5 min in an 1850 F salt bath. The elements will be evaluated by metallographic examinations, chemical analyses, burst tests of compartments, bend and peel tests, intercompartmental leakage tests, and corrosion tests of purposely defected compartments.

Three elements containing sprayed-graphite-coated cores which were buffed have been assembled using the protective-container technique. These elements will be pressure bonded at 1550 F and 10,000 psi for 4 hr.

N-1

N. DEVELOPMENT FOR THE MGCR

W. H. Goldthwaite

Research in support of the Maritime Gas-Cooled Reactor Program is reported in this section. The development and evaluation of candidate fuels and the effects of radiation on corrosion and carbon transport by coolant impurities are being studied.

FABRICATION AND IRRADIATION OF FUEL MATERIALSFabrication of BeO-UO₂ Fuel Elements

A. K. Smalley, W. C. Riley, and W. H. Duckworth

Fuel-element cores of UO₂ particles dispersed in a densely sintered BeO matrix are being developed.

During April, experimental pellets were prepared for encapsulation by the procedure described in BMI-1315. The fuel loading was about 20 volume per cent of 30 per cent enriched UO₂. Bulk densities of eleven pellets ranged from 88.8 to 90.9 per cent of the calculated theoretical density of the mixture, their average bulk density being 89.4 per cent of theoretical.

Processes for increasing the bulk density of the BeO-UO₂ ceramics were explored. Preliminary results with bodies containing about 20 volume per cent UO₂ indicated that bulk densities of about 98.5 per cent of theoretical can be obtained through the use of organic-bonded sinterable UO₂ particles.

Fabrication of Graphite Fuel ElementsW. A. Hedden, A. B. Tripler, Jr., W. C. Riley,
and W. H. Duckworth

The objective of this research is to develop improved techniques for fabrication of graphite-matrix fuel-element cores containing a uniform dispersion of UC or UC₂ particles. The fuel content desired in the core is an amount equivalent to 20 volume per cent of UO₂.

In work reported previously, batch compositions were established that yielded the desired fuel content in compacts after baking at about 2300 F in an inert atmosphere.

N-2

During this report period, a limited quantity of UC and UC₂, made from 30 per cent enriched uranium, was obtained. This material was crushed and screened to minus 100 plus 200-mesh particles and incorporated into a graphite-pitch mixture in accordance with procedures established in preliminary experiments. Compacts then were formed and baked at a temperature of about 2300 F. The fuel content of the baked compacts, calculated on the basis of an equivalent volume of UO₂, was about 19.8 and 19.0 volume per cent for samples containing UC₂ and UC, respectively. The compacts will be submitted for neutron-irradiation studies.

Progress was made in the study to establish the effect of variations in binder-filler ratios on the properties of baked compacts. It is expected that this study will be completed next month.

Development of BeO-Clad UO₂ Pellets

A. K. Smalley, W. C. Riley, and W. H. Duckworth

Special equipment was made for fabricating BeO-clad UO₂ particles. The equipment has been tested, and experiments are in progress on developing low-porosity BeO cladding.

Radiation-Effects Study of Potential Fuels

J. E. Gates, C. V. Weaver, and A. F. Dickerson

A capsule loaded with compacts of (1) UO₂ in a BeO matrix, (2) UC in a graphite matrix, and (3) UC₂ in a graphite matrix is being irradiated in the BRR. The experiment is designed to study the effects of these potential fuels under conditions simulating those in the MGCR. Four pellets of each material are sealed in stainless steel tubes under a helium atmosphere. Three pairs of specimens are included in the capsule, which is equipped with thermocouples and heaters. The specimens were expected to operate at surface (cladding) temperatures of 1500 F and a heat flux of the order of 185,000 Btu/(hr)(ft²).

At the conclusion of 12 days of irradiation, one BRR cycle, the performance of the capsule was generally satisfactory. The center of the specimen array is about 4 in. below the actual flux peak. As a result of this, plus heat and losses, the surface temperature and heat flux of the bottom specimen are about 20 and 30 per cent, respectively, off the values specified above. However, temperatures and heat fluxes of the other five specimens are within 5 and 15 per cent, respectively. Since these are so close, the capsule will not be moved.

The experiment will remain in the BRR for three more cycles, 36 days of irradiation time. It is anticipated that the experiment, including a postirradiation examination of the specimens, will be completed by June 30.

N-3 and N-4

CORE-MATERIALS IRRADIATION PROGRAM

N. E. Miller and W. S. Diethorn

A study is being made of potential carbon-transport, metal-oxidation, and metal-carburization problems which may be associated with an unclad-graphite-moderated helium-cooled reactor system.

The GA2-1 capsule containing the four quartz tori described in previous BMI reports was inserted in the core of the BRR for irradiation on April 8, 1959. Heater failures shortly after the reactor came up to power curtailed the experiment. Examination of all accessible heater leads and connections did not reveal the cause of the failure.

A second capsule, GA2-2, has been prepared and will be inserted in the BRR on May 7, 1959. In this experiment, the heaters will be brought to the operating temperature after insertion in the BRR core before the reactor is brought to power. If heater failures occur, the capsule can be withdrawn before irradiation for a more complete examination.

O-1 and O-2

O. ENGINEERING ASSISTANCE TO KAISER ENGINEERS

Reactor Flow Studies

L. J. Flanigan and H. R. Hazard

Studies of flow in a quarter-scale model of the Partially-Enriched Gas-Cooled Power Reactor are being conducted at Battelle to provide design data for the prototype. Previously reported work includes construction of the plastic-model parts, the model core, and the parts for the test setup.

In April, construction on all three phases was continued. At Battelle, assembly of the core is about 95 per cent complete and work on the test setup is about 99 per cent complete. Construction of the plastic-model parts by a vendor was delayed unexpectedly by allergic reactions of personnel making plastic layups to the chemicals. Delivery to Battelle is now scheduled for May 15, 1959.

In May, core orifices will be calibrated, and the model will be assembled. It is anticipated that tests can begin a few days after delivery of the plastic-model parts.

P-1

P. DEVELOPMENTAL STUDIES FOR THE SM-2

S. J. Paprocki

This portion of the report covers work being performed to assist Alco Products in the development of fuel, absorber, and suppressor materials for the SM-2.

The materials studies have been concerned with the fabrication of stainless steel- UO_2 dispersion fuel elements for irradiation testing. The problems encountered in the fabrication of these elements such as incorporation of boron as a burnable poison, and stringering of the UO_2 fuel will also be present in the fabrication of the full-scale fuel elements. The dispersion of ZrB_2 in the core matrix combined with a vacuum-sintering treatment has been selected as the reference method for incorporating boron into the SM-2 elements.

Irradiation specimens have been fabricated and evaluated, and some of the specimens that are planned for irradiation have been encapsulated. It is planned to irradiate the specimens in the ETR in order to obtain a neutron flux of 3×10^{14} nv so that high burnups of the uranium-235 can be achieved in a relatively short exposure time.

Development of Fuel Materials

S. J. Paprocki, D. L. Keller, G. W. Cunningham,
J. B. Fox, D. E. Lozier, and W. M. Pardue

Fuel materials have been selected and reference fabrication procedures are being developed for SM-2 fuel elements, although, at the present time, major emphasis is being placed on the preparation of irradiation specimens. Reference fuel elements contain cores of approximately 26 w/o spherical UO_2 (Mallinckrodt) and 1.1 w/o ZrB_2 dispersed in a Type 347 prealloyed stainless powder matrix. Type 347 cladding (0.005 in. thick) is bonded to the core by a roll-cladding process.

In the initial studies, ZrB_2 powders were prefired at 2300 F in hydrogen before blending, and the core compacts were sintered in hydrogen at 2200 F (-100 F entrance dew point, -35 F exit dew point) in order to adapt the process to present commercial practice. However, erratic results have been obtained. Boron contents of the ZrB_2 have dropped from 17.5 w/o to values of 15.5 to 16.9 w/o during the prefiring treatment, and boron losses of 0 to 50 w/o have occurred during the sintering operation. These losses are apparently related to both the purity of the powders and the purity of the hydrogen atmosphere. Future studies are planned to determine the effect of various impurities in the ZrB_2 , and losses will be measured after sintering in a vacuumtight system with calcium hydride or uranium hydride as the source for hydrogen. However, this investigation cannot be completed until after irradiation specimens are prepared. On the other hand, chemical analyses show little or no loss when ZrB_2 is prefired in vacuo at 2300 F and core compacts are sintered in vacuo.

Comparison of specimens shown in Table P-1 shows the effect of sintering atmosphere. Erratic results were obtained in hydrogen and small consistent losses were

obtained for specimens sintered in vacuo at 2200 F. In this case, a small loss was expected, since the ZrB_2 was prefired in hydrogen and contained a heavy oxide coating. The boron content of the ZrB_2 had been reduced from 17.5 to 16.1 w/o by the prefiring. Analysis of another specimen that contained vacuum-prefired ZrB_2 and was sintered at 2200 F in vacuo gave a value of 0.229 w/o boron compared with the nominal amount of 0.220 w/o boron.

TABLE P-1. BORON ANALYSES AS RELATED TO SINTERING ATMOSPHERE

Description of Specimen	Sintering Conditions	Boron Analysis, w/o
1 w/o ZrB_2 in prealloyed matrix	2 hr at 2000 F in hydrogen	0.127
Type 347 matrix (0.161 w/o boron)	2 hr at 2000 F <u>in vacuo</u>	0.166
	2 hr at 2200 F in hydrogen	0.134
	2 hr at 2200 F <u>in vacuo</u>	0.153
26 w/o UO_2 -0.1 w/o ZrB_2 in prealloyed Type 347 matrix (0.161 w/o boron)	2 hr at 2000 F in hydrogen	0.168
	2 hr at 2000 F <u>in vacuo</u>	0.169
	2 hr at 2200 F in hydrogen	0.109
	2 hr at 2200 F <u>in vacuo</u>	0.156

The appearance of microstructures can also be related to the boron content of the ZrB_2 and the boron loss during sintering. The characteristics of individual ZrB_2 particles will vary from particle to particle and, consequently, the appearance of the particles and the presence of secondary phases will vary in the same specimen. The porosity and, to a certain extent, the impurity of ZrB_2 particles may vary even within the same batch. The ZrB_2 is prepared by reacting mixtures of ZrO_2 , B_4C , and B_2O_3 to form a spongelike cake. When coarse particles are used, variation in porosity and carbon content can be expected. It is also possible to have variation in boron content, but differences of 1 to 2 w/o probably do not change the characteristics of the ZrB_2 , while a few tenths of a per cent of carbon could cause considerable reaction. Therefore, descriptions of the general appearance of a specimen do not necessarily describe the worst or best ZrB_2 particles.

Using a lot of ZrB_2 which initially contained 17.5 w/o boron and 0.55 w/o carbon, compacts have been sintered under several different conditions, and a comparison of their microstructures has been made. The poorest quality ZrB_2 dispersion was obtained in a specimen sintered at 2200 F in hydrogen which contained ZrB_2 that had been prefired in hydrogen at 2300 F, resulting in a compound with 15.5 w/o boron. In this specimen, an oxide phase ranging from a heavy layer to complete disappearance of the ZrB_2 could be observed, and a heavy precipitate similar to that observed in B_4C specimens could be detected. In another specimen which was identical except that the ZrB_2 contained 16.9 w/o boron after prefiring, a few particles could be detected which did not contain oxide or other secondary phases, while most of the particles contained a solid but thin oxide layer along the surface. Also, some of the unidentified precipitate could be detected in the core matrix. Comparison of vacuum-sintered specimens

P-3

indicates that little or no change in the ZrB_2 occurs during sintering. When vacuum-prefired ZrB_2 powder (17.4 w/o boron) was used, a high percentage of the ZrB_2 particles showed no change except for a thin intermittent layer of oxide on the surface of the particle. In some cases, around a few particles, a small amount of the unidentified precipitate was detected. When ZrB_2 prefired in hydrogen was used, similar results were obtained except that the oxide phase and the precipitate were somewhat increased. Comparison of specimens sintered at 2000 F showed similar results except that the amount of oxide and the unknown phase was decreased. No oxide- or boron-containing phase other than ZrB_2 could be observed in vacuum-sintered specimens.

Three capsule loadings of irradiation specimens have been fabricated. Since the difference in sintering conditions had not been fully evaluated, two sets of specimens were prepared. One set was sintered in hydrogen and the other set was sintered in vacuo. Chemical analyses of roll-clad specimens are listed in Table P-2. A single pack containing five specimens was made of each type, with two specimens to be used for irradiation, one specimen to be used for chemical analyses, one specimen to be used for metallography, and one specimen to be used as a control specimen for post-irradiation evaluation. Roll-clad specimens contain cores 0.500 by 1.000 by 0.030 in. and are clad with 0.005-in. Type 347 stainless. The machined size of the finished specimens is 2.606 (suppressor specimens) or $1.506 \pm 0.040 \pm 0.001$ by 0.5625 ± 0.013 or -0.000 in. On the basis of the chemical analyses and metallographic examinations, only those specimens sintered in vacuo will be used for irradiation.

In addition to reference irradiation specimens, several alternates are being prepared. Niobium diboride has been selected as the alternate boride and specimens are being prepared by the same method described in BMI-1330 except that sintering and roll-cladding temperatures of 2000 F are being used in order to prevent reaction between the matrix and NbB_2 . Boron nitride is also being considered for use, but sufficient data will not be available to permit fabrication of specimens for the irradiation capsules now being prepared.

Highly loaded specimens containing up to 40 w/o UO_2 or UN and 2 w/o ZrB_2 dispersed in an elemental matrix are also being prepared. The elemental matrix contains 0.18 w/o Lunex chromium, 9 w/o carbonyl nickel, and a hydrogen annealed electrolytic iron powder. These powders were selected because of their high purity and low oxygen content. In order to prevent reaction and loss of boron, specimens are sintered at 2000 F, but a 2300 F anneal after hot rolling is required to place all the chromium in solution.

Another alternate method of incorporating the boron in the fuel element consists of using a 0.46 w/o boron alloy for edge cladding. An alloy analyzed as 0.44 w/o boron has been prepared, and irradiation specimens are being fabricated.

Specimens containing B_4C loadings comparable to both SM-1 and SM-2 fuel plates have been prepared and will be irradiated in order to correlate data concerning SM-1 plates with data for reference SM-2 specimens.

TABLE P-2. LIST OF FABRICATED IRRADIATION TEST SPECIMENS

Description of Specimen	Heat-Treatment Atmosphere	Boron Content, w/o		Boron Analysis of As-Rolled Plate, w/o
		Reference	Nominal	
Hydrate $\text{UO}_2\text{-B}_4\text{C}$	Hydrogen	0.20	0.22	0.192
Hydrate $\text{UO}_2\text{-ZrB}_2$	Vacuum	0.20	0.22	0.199
Hydrate $\text{UO}_2\text{-ZrB}_2$	Hydrogen	0.20	0.22	0.193
Spherical $\text{UO}_2\text{-ZrB}_2$	Hydrogen	0.20	0.22	0.212
Spherical $\text{UO}_2\text{-ZrB}_2$	Vacuum	0.20	0.22	0.214
Spherical $\text{UO}_2\text{-ZrB}_2$, suppressor	Hydrogen	0.20	0.22	0.251
Spherical $\text{UO}_2\text{-ZrB}_2$, suppressor	Vacuum	0.20	0.22	0.240
Spherical $\text{UO}_2\text{-ZrB}_2$, green compact	Hydrogen (ZrB_2)	0.20	0.22	0.203
Spherical $\text{UO}_2\text{-ZrB}_2$, green compact	Vacuum (ZrB_2)	0.20	0.22	0.209
Spherical $\text{UO}_2\text{-ZrB}_2$, (one-half loading)	Hydrogen	0.10	0.11	0.073
Spherical $\text{UO}_2\text{-ZrB}_2$, (one-half loading)	Vacuum	0.10	0.11	0.095

P-5 and P-6

Encapsulation Studies

W. E. Murr, A. K. Hopkins, D. B. Hamilton, and J. H. Stang

During April, the fabrication of two SM-2 specimen capsules was nearly completed and the assembly of another capsule entered the specimen-loading stage. Also, machining of components for four additional capsules was completed. It is anticipated that the two initial capsules (BMI-32-1 and BMI-32-2) can be shipped to the ETR by May 15; each of these capsules contains four clad fueled (28 w/o and 40 w/o UO_2 dispersed in stainless) specimens and one clad specimen containing Eu_2O_3 plus fuel. As mentioned in previous reports, design conditions for the fuel irradiations include a specimen surface temperature of 650 F and burnups to 37 a/o and 77 a/o; the unperturbed thermal-neutron-flux specification is 3×10^{14} nv, which is available in the ETR beryllium reflector.

Other recent activity in the program has been along the following lines:

- (1) Close liaison with various manufacturers of sheathed resistance heaters to study further heater-integrity problems. Heater integrity is an important concern in this program since it is necessary to incorporate considerable auxiliary heating capacity (nominally 12 kw) into the capsules to maintain specimen temperatures as burnup progresses.
- (2) Fabrication of nuclear-mock-up capsules for ETR study purposes and shipment of these mock-ups to the ETR.
- (3) Additional studies of capsule heat transfer to appraise uncertainties that must be dealt with in the interpretation of capsule temperature data during the irradiation. Capsule temperatures will be monitored by thermocouples located near the specimens and will be used to estimate specimen surface temperature and rate of fuel burnup.
- (4) The operation of a heat-transfer mock-up experiment in the laboratory to confirm heat-transfer analyses and to investigate the effectiveness of the heater configuration in maintaining design specimen temperatures. Data from mock-up runs to date indicate good agreement between actual and predicted performance.

Q-1

Q. GAS-COOLED REACTOR PROGRAM

D. L. Keller

Studies for Aerojet-General Nucleonics (AGN) directed toward the development of compact gas-cooled reactors for military applications are reported in this section.

MATERIALS DEVELOPMENT PROGRAM

The evaluation of irradiated stainless steel- UO_2 and graphite- UO_2 and $-\text{UC}_2$ fuel specimens and the encapsulation and irradiation of solid UO_2 pins, stainless steel-UN and $-\text{UO}_2$ plates, and graphite- UO_2 pins have continued.

A program concerned with the preparation of UO_2 pellets for use in in-pile-loop assemblies was initiated this month.

Effects of Irradiation

J. H. Saling, J. E. Gates, and R. F. Dickerson

A study of the radiation stability of fuel-element materials for compact gas-cooled reactors includes (1) the evaluation of encapsulated stainless steel- UO_2 specimens, (2) the evaluation of encapsulated fueled-graphite specimens, and (3) the evaluation of in-pile-loop subassemblies.

Stainless Steel- UO_2 Capsule Program

This program involves the evaluation of encapsulated and irradiated specimens of 25 and 30 w/o UO_2 dispersed in stainless steel and clad with stainless steel. The evaluation of specimens from this program has been completed.

Fueled-Graphite Capsule Program

This program involves the evaluation of irradiated specimens of UO_2 and UC_2 dispersed in graphite. The evaluation of specimens from this program has been completed.

In-Pile-Loop Subassemblies

GCRE-MARK 1-1-T. A radiochemical burnup analysis of a section of Fuel Plate D-II which was removed from the axial center of the fuel plate indicates a

Q-2

uranium burnup of 0.4 a/o. The results of a radiochemical burnup analysis on a section which was removed from the axial center of Fuel Plate A-1 will be reported as soon as they become available.

Encapsulation Studies

J. H. Stang, P. B. Shumaker, and J. C. Smith

Three high-temperature irradiation programs involving a total of four capsules are under way. The first program involves the irradiation of four clad flat-plate specimens [three containing dispersions of highly enriched UN (28 w/o) and one containing UO_2 (30 w/o) in stainless steel] in a single capsule (BMI-28-1). The second program includes two capsules (BMI-27-1 and BMI-27-2), each containing six Inconel-clad UO_2 (35 w/o enrichment) pins along the capsule axis. In the third program, clad UO_2 -graphite (8 w/o UO_2 , highly enriched) specimens are to be irradiated in a single capsule (BMI-29-1). At the present time, BMI-28-1, BMI-27-1, and BMI-27-2 are being irradiated at the MTR; graphite specimens for BMI-29-1 will be clad at Battelle during May. The capsule is scheduled to be loaded during June.

Irradiation of Capsule BMI-28-1 began April 10 at the start of MTR Cycle 120. Table Q-1 shows representative thermocouple temperatures within the capsule during the first irradiation cycle. Inasmuch as the specimen-surface-temperature conditions are within the 1650 ± 50 F range originally specified, it has not been necessary to supplement the fission heating with auxiliary heat from the bank of resistance heaters incorporated in the capsule. Based on the present flux estimates, the target burnup of 12 a/o uranium-235 (for peak-flux specimens) will be reached in five reactor cycles.

TABLE Q-1. REPRESENTATIVE DATA FOR CAPSULE BMI-28-1^(a) DURING MTR CYCLE 120

Thermocouple	Thermocouple Temperature, F	Calculated Specimen Surface Temperature, ^(b) F
1 ^(c)	1600	1620
3	1605	1625
4	1730	1750
5	1700	1720
6	1570	1590

(a) Capsule is located in MTR Facility A-40 in a single-hole A piece.

(b) Unperturbed thermal neutron flux estimates on basis of heat-transfer analyses:

Two center specimens 0.9×10^{14} nv
End specimens 0.8×10^{14} nv.

(c) The four specimens are strung along the capsule axis; Thermocouples 1 and 3 are located in the NaK bath on opposite sides of the top specimen, Thermocouple 4 is opposite Specimen 2, Thermocouple 5 is opposite Specimen 3, and Thermocouple 6 is opposite the bottom specimen.

Q-3

Table Q-2 presents representative temperature data for Capsules BMI-27-1 and BMI-27-2 during Cycle 120. The axial temperature profile of BMI-27-2 has remained virtually unchanged since its insertion during the start of Cycle 119. As indicated by the data presented, the profile is characterized by high temperatures for the end specimens and relatively low temperatures for those located in the center zone of the capsule. During Cycle 120 shutdown, BMI-27-1 was inserted into the reactor. However, as the reactor was brought up to power during startup, the local temperature levels along the capsule axis were higher than anticipated (the specimen surface design temperature was 1700 ± 100 F) even though the quoted peak unperturbed flux in A7NW is substantially lower than the normal capsule design flux (1.1×10^{14} nv for both BMI-27-1 and BMI-27-2). Consequently, the capsule was not positioned with its mid-plane in the high-flux zone as originally intended but was raised to the position indicated in Table Q-2.

During the past month, intensive study has been made of the performance of these capsules inasmuch as in both cases it has been substantially different than that predicted on the basis of design calculations. This study has yielded a partial explanation for the observed behavior. In the first place, a computational error was found in the Bessel function manipulation involved in the solution of the heat-transfer analysis used in the design of these capsules. This error was such that the helium-gap thermal resistance (between the inner specimen-NaK container and the outer water-contacting shell) in the capsule is too high by about 30 per cent. This factor, in part, accounts for the fact that the temperatures in the capsules are higher than expected in view of the reactor-quoted fluxes.

In the recent analyses of performance, close attention has also been paid to effects stemming from axial heat-transfer biasing incorporated into the capsules. This consisted of increasing the resistance offered by the helium gap in the axial zone of the top and bottom two specimens by about 12 per cent over that in the axial zone of the middle two specimens and was done to compensate for the usual axial flux profile. While this biasing offers a partial explanation for the axial temperature profile of BMI-27-2 cited above, it appears to fully account for it only if the flux peak is located well below its normal position (about 21 in. below the lattice) in the irradiation space. However, no reason is evident that the flux profile should have such a characteristic.

Capsule relocation of BMI-27-1 is being carefully considered, and further analyses of the situation will be made during May to arrive at a recommendation for relocation which will permit more uniform specimen burnup (to the desired 9.0 w/o uranium-235 for BMI-27-1 and 5.8 a/o uranium-235 in BMI-27-2) without the risk of unacceptably low specimen temperatures.

Fabrication of UO₂ Pellets

H. D. Sheets and A. G. Allison

The objective of this program is to prepare suitable enriched UO₂ specimens for irradiation testing as part of the GCRE program. The tabulation on page Q-5 summarizes the fuel-pellet requirements:

TABLE Q-2. REPRESENTATIVE DATA FOR CAPSULES BMI-27-1 AND BMI-27-2 DURING MTR CYCLE 120

Capsule	Reactor Position	Distance From Lattice, in.		Approximate Reactor-Quoted Peak Flux, 10^{14} nv	Thermocouple(a)	Thermocouple Temperature(b), F	Estimated Specimen Surface Temperature, F
		Top Specimen	Bottom Specimen				
BMI-27-1	A7NW	3	16	0.80	1	590	620
					2	630	660
					3	835	865
					4	--	--
					5	1600	1630
					6	1635	1665
BMI-27-2	A30SE	14	29	0.80	1	1500	1530
					2	--	--
					3	1200	1230
					4	1340	1370
					5	1500	1530
					6	1625	1655

(a) Thermocouple 1 is located in NaK bath opposite Specimen 1 (top of stack), Thermocouple 2 is opposite Specimen 2, etc.

(b) Temperatures in BMI-27-2 are being maintained by an auxiliary heater input of approximately 1-1/2 kw.

Q-4

Q-5

<u>Enrichment, per cent U²³⁵O₂</u>	<u>Outside Diameter, in.</u>	<u>Inside Diameter, in.</u>	<u>Total Length of Pellets, in.</u>
25	0.160 ± 0.002	--	308
	0.160 ± 0.002	0.048 ± 0.004	618
50	0.160 ± 0.002	--	176
	0.160 ± 0.002	0.048 ± 0.004	352

Bulk densities of about 94 per cent of theoretical are desired.

The UO₂ for use in this program was received from Aerojet. In order to choose fabrication conditions for making the required pellets, a series of experiments in which ball-milling time and forming pressure were varied was carried out. The results are presented in Table Q-3. The UO₂ was crushed to pass through a 20-mesh screen and then ball milled in 100-g batches in a 1-qt mill with a natural-rubber lining using Al₂O₃ balls. The powder was mixed with 3 w/o camphor, and the pellets were pressed in a hardened steel die. The pressed pellets were sintered at 3000 F in a hydrogen-atmosphere molybdenum-wound resistance furnace.

On the basis of this information and previous experience, the following conditions have been selected for fabrication of the required specimens:

<u>Enrichment, per cent U²³⁵O₂</u>	<u>Ball-Milling Time, hr</u>	<u>As-Formed Density, g per cm³</u>
25	4	5.0
50	15	5.3

About 50 in. of the solid, 50 per cent enriched pellets have been prepared.

IN-PILE-LOOP PROGRAM

G. A. Francis

During this report period, preparation for operation of the two in-pile recirculating gas loops was continued.

The Battelle Research Reactor loop was reinstalled in the reactor pool and minor loop maintenance and instrument check-outs have been started. On the Engineering Test Reactor loop, which is designated BMI-16, installation activity was continued at the reactor site and the construction of auxiliary equipment was continued at Battelle. Details of the activity on the various phases of the loop program are described in the following paragraphs.

TABLE Q-3. EFFECT OF PROCESSING CONDITIONS ON DIAMETRAL SHRINKAGE AND BULK DENSITY OF UO_2 PELLETS(a)

Specimen	Enrichment, per cent	Ball-Milling Time, hr	Forming Pressure, psi	As-Formed Bulk Density, g per cm^3	Diametral Shrinkage, per cent	Fired Bulk Density	
						G per Cm^3	Per Cent of Theoretical
1-1	50	4	10,000	4.7	23.7	10.1	92
1-2	50	4	20,000	5.0	21.5	10.1	92
1-4	50	4	40,000	5.5	18.8	10.2	93
2-1	50	15	10,000	4.9	22.7	10.2	93
2-2	50	15	20,000	5.3	20.8	10.3	94
2-4	50	15	40,000	5.8	18.6	10.3	94
3-1	25	4	10,000	4.7	23.8	10.3	94
3-2	25	4	20,000	5.0	21.8	10.3	94
3-4	25	4	40,000	5.5	19.3	10.3	94
4-1	25	15	10,000	5.1	21.9	10.3	94
4-2	25	15	20,000	5.4	20.2	10.4	95
4-4	25	15	40,000	5.8	18.1	10.4	95

(a) Results are averages for two groups of two specimens each. Bulk densities were calculated from the weights and dimensions of the specimens. Theoretical density of UO_2 was taken as 10.98 g per cm^3 .

Q-7

BRR Loop Program

S. J. Basham and W. H. Goldthwaite

The BRR loop was removed from the pool late last year for modifications directed toward an increase in specimen heat generation and an increase in gas temperature at the specimen inlet. The necessary modifications were completed during March and the loop was reinstalled in the reactor pool during this research period. The auxiliary equipment, instruments, controllers, and pneumatic equipment were calibrated and adjusted. The system was operated satisfactorily for several days. The primary problem remaining is that of gas leakage from the primary coolant system. The source of the leaks have been identified and will be corrected during May. The problem involved in making these repairs is that the BRR operates on a 2-week cycle with 12 days at power and 2 days of shutdown. Repair of the loop can be performed only during reactor shutdowns when the loop is moved to the back pool, which can be drained.

Present plans would have a fuel specimen ready for irradiation starting near the middle of June. The loop should be ready to receive the specimen when it becomes available.

ETR Loop Program

J. V. Baum, W. J. Stevens, and E. O. Fromm

Major activity on this program was associated with installation of the loop and the construction and delivery of auxiliary equipment. The two irradiated aluminum tensile specimens were returned to the hot cell but have not yet been evaluated.

Loop Installation

Activity at the reactor site centered around the installation of lead wires and utility connections in preparation for the cold check of the loop assembly. Since the reactor nozzle from which leads will be pulled, the machinery cubicle, and the console area are widely separated within the reactor building, the connections have proved an expensive and time-consuming operation.

During April installation progressed to the point where the cold check of the system could begin. Initial checks showed that the replacement of cooling coils in the blower-motor housings would be required. This replacement will be completed during the first week of May. Additional minor changes requested by Phillips Petroleum Company have also been made. Further major mechanical work will be done at the time of in-pile-tube insertion.

Q-8

The cold-check and operator-training period should consume the month of May. Scheduling problems being encountered at the reactor will determine the period of initial loop operation since the loop should be ready for tube insertion by the end of May and the first test element is now at the reactor. The present reactor schedule places the start of tube insertion on July 7.

Auxiliary Equipment

The two fuel specimen-transfer and -shipping casks were filled with lead early in the report period. In a test of the drawbar-cutoff mechanism, a 3/4-in. -diameter stainless steel tube with a wall thickness of 0.083 in. was sheared satisfactorily with each cask. The casks were shipped to the ETR on April 20.

The attenuator blocks based on new reactor flux data are nearing completion and should be shipped to the reactor by May 8. All BMI-16 equipment designed and built at Battelle should be shipped to the reactor site during May. The items to be shipped are three sets of attenuators and a dolly to be used in handling the test specimen and attached drawbar.

RWD/CRT:all