MASTER

NAA-SR-MEMO COVER SHEET

AUTHOR
E. L. Reed

NAA-SR-MEMO-11225

(This Document Contains 9 Pages.)
(This is Copy 22 of Series)

This report was prepared as an account of work sponsored by the United States Government. Neither the United States nor the United States Atomic Energy Commission, nor any of their employees, nor any of their contractors, subcontractors, or their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness or usefulness of any information, apparatus, product or process disclosed, or represents that its use would not infringe privately owned rights.

NOTICE

THIS MATERIAL CONTAINS INFORMATION RELATING TO THE NATIONAL DEFENSE OF THE UNITED STATES WITHIN THE MEANING OF THE SPY ACT OF 1950, 18 U.S.C. 793 AND 794. IT IS UNLAWFUL TO REVEAL OR THE REVELATION OF ITS CONTENTS IN ANY MANNER TO AN UNAUTHORIZED PERSON IS PROHIBITED BY LAW.

CLASSIFICATION TYPE
(RD OR DI)

NAA-SR-MEMOs are working papers and may be expanded, modified, or withdrawn at any time, and are intended for internal use only.

THIS REPORT MAY NOT BE PUBLISHED WITHOUT THE APPROVAL OF THE PATENT BRANCH, AEC

-LEGAL NOTICE

This report was prepared as an account of Government sponsored work. Neither the United States, nor the Commission, nor any person acting on behalf of the Commission:

A. Makes any warranty or representation, express or implied, with respect to the accuracy, completeness, or usefulness of the information contained in this report, or that the use of any information, apparatus, method, or process disclosed in this report may not infringe privately owned rights; or

B. Assumes any liabilities with respect to the use of, or for damages resulting from the use of information, apparatus, method, or process disclosed in this report.

As used in the above, "person acting on behalf of the Commission" includes any employee or contractor of the Commission, or employee of such contractor, to the extent that such employee or contractor of the Commission, or employee of such contractor prepares, disseminates, or provides access to, any information pursuant to his employment or contract with the Commission, or his employment with such contractor.

Classification Cancelled

~~or changed to UNCL~~

By Authority Of

Bv
7 e k e

Exempt from CCRP Re-review Requirements
(per 7/22/82 Duff/Caudle memorandum)

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

GROUP 3

~~DOWNGRADED AT 12 YEARS~~

~~INTERVALS: NOT AUTOMATIC~~

~~DECLASSIFIED~~

~~CONFIDENTIAL~~

CLASSIFICATION LEVEL
(S, C OR U)

DO NOT REMOVE THIS SHEET : UNCLASSIFIED

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency Thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

DISCLAIMER

Portions of this document may be illegible in electronic image products. Images are produced from the best available original document.

~~CONFIDENTIAL~~

UNCLASSIFIED

ATOMICS INTERNATIONAL A Division of North American Aviation, Inc.		NAA-SR-MEMO- TOP SECRET 11225	APPROVALS <i>[Signature]</i>
TECHNICAL DATA RECORD		PAGE 1 OF 9	
AUTHOR	DEPT. & GROUP NO.	DATE	
E. L. Reed <i>ELR</i>	732-20	4/5/65	
TITLE		GO NO.	
Post Test Examination of P-Elements in T/E Pumps DEV-4 and DEV-5 (Title Unclassified)		7561	
		S/A NO.	TWR
		2321	0908000
		SECURITY CLASSIFICATION	
		(CHECK ONE BOX ONLY)	
		(CHECK ONE BOX ONLY)	
		RESTRICTED DATA ☐	
		DEFENSE INFO. ☒	
		AUTHORIZED CLASSIFIER SIGNATURE <i>[Signature]</i> DATE 4/13/65	
PROGRAM	SUBACCOUNT TITLE		
SNAP 10A	T/E Pump and Emissivity		
Flight Test	Coatings		
DISTRIBUTION			
Hq			
J. Addison	2		
G.V. Alm	1		
M.H. Binstock	1		
S.M. Cobb	1		
J.R. Crosby	SS36		
K.A. Davis	SS36		
V.A. deProsse	1		
H.M. Dieckamp	2		
A.N. Gallegos	SS36		
R.B. Gordon	2		
R.D. Keen	SS36		
W.D. Leonard	SS36		
E.L. Reed	1		
D.S. Thompson	2		
P.S. Vandervort	5		
R.F. Wilson	2		
A. Zonder	5		
STATEMENT OF PROBLEM			
T/E Pump DEV-4 was tested for 967 hours. Pump DEV-5 was run for approximately 2160 hours. Both pumps were fabricated with the older type, tin-free, Lead Telluride P-elements. It was desired to examine the P-elements from these pumps and compare them with the tin-containing type of P-elements examined in recent pumps.			
ABSTRACT:			
Photomicrographs of the cold side of the P-elements from T/E Pumps DEV-4 and DEV-5 are exhibited and discussed. The results were not conclusive; but there appeared to be significantly less contamination in the tin-free lead telluride materials from these pumps, than has been observed in the lead tin telluride type of P-elements after comparable periods of performance testing.			
<p>THIS MATERIAL CONTAINS INFORMATION AFFECTING THE NATIONAL DEFENSE OF THE UNITED STATES WITHIN THE MEANING OF THE Espionage LAWS, TITLE 18 U.S.C. SECTION 793, ITS TRANSMISSION OR THE REVEALING OF ITS CONTENTS IN ANY MANNER TO AN UNAUTHORIZED PERSON IS PROHIBITED BY LAW.</p>			

~~CONFIDENTIAL~~ UNCLASSIFIED

~~CONFIDENTIAL~~

~~UNCLASSIFIED~~

NO. NAA-SR-MEMO-11225

DATE 4/5/65

PAGE 2 OF 9

ATOMICS INTERNATIONAL

A Division of North American Aviation, Inc.

TABLE OF CONTENTS

	<u>Page</u>
ABSTRACT.	1
TABLE OF CONTENTS	2
LIST OF FIGURES	3
I. INTRODUCTION	4
II. METALLOGRAPHIC EXAMINATION OF P-ELEMENT SECTIONS.	5
III. SUMMARY OF RESULTS.	6
IV. CONCLUSIONS	6
V. RECOMMENDATIONS	6
VI. REFERENCES.	7

~~CONFIDENTIAL~~

~~UNCLASSIFIED~~

~~CONFIDENTIAL~~

NO. NA-68-MEMO-11225

ATOMICS INTERNATIONAL

A Division of North American Aviation, Inc.

DATE 4/5/65

PAGE 3 OF 9

LIST OF FIGURES

		<u>Page</u>
FIGURE 1	Pump DEV-4. Cold Side of P-Type PbTe Elements. Unetched.	8
FIGURE 2	Pump DEV-5. Cold Side of P-Type PbTe Elements. Unetched.	9

~~CONFIDENTIAL~~

DECLASSIFIED

ATOMICS INTERNATIONAL

A Division of North American Aviation, Inc.

NO. ~~CONFIDENTIAL~~ NAA-SR-MEMO-11225

DATE 4/5/65

PAGE 4 OF 9

I. INTRODUCTION

SNAP 10A Thermoelectric Pumps Number DEV-4 and DEV-5 were two of the early development pumps which were fabricated with sodium-doped, tin-free lead telluride material for the P-type T/E elements. Standard, lead-iodide-doped lead telluride material was used for the N-type T/E elements. Later T/E pumps have been fabricated with a sodium-doped, lead-tin-telluride material for the P-type elements. There has been no change in the N-type of material.

Post test metallographic examination of pumps fabricated with the lead-tin-telluride type of P-elements have shown a massive accumulation of contaminants visible in the cold side of the P-type, PbSnTe material. Very little contamination has been observed in the N-type, PbTe, T/E elements. This contamination of the tin-containing type of P-material has been attributed to the reaction of tellurium and/or tellurium-tin vapors with the copper metal strap material on the hot side of the T/E elements, with subsequent migration of the tellurium-copper-tin type of compounds to the colder side of the T/E elements. Microprobe studies of this contaminating phenomenon and photomicrographs showing the appearance of this type of massive contamination have been reported in some recent TDR-MEMO publications⁽¹⁾.

It was desired to examine the tin-free, P-type of T/E elements from Pumps DEV-4 and DEV-5 to see if these also showed an accumulation of contaminants in the cold side of the T/E material. The P-elements were cut away from these two pumps with a hack saw and mounted in an Epoxy casting resin. Then sections of these "potted" elements were polished and examined to determine the extent of contamination visible in the cold side of the PbTe T/E Materials. None of the other components in the pump assemblies were examined because the question of element contamination was the only item considered to be of interest at this time.

Pump DEV-4 was performance tested at design temperature for a period of 967 hours. Pump DEV-5 was run under similar conditions for a period of 2160 hours.

Photomicrographs of the cold side of the T/E element materials in these pumps are shown in the report. These are discussed and a tentative conclusion drawn comparing these tin-free elements with the PbSnTe type of P-elements now in current use.

ATOMICS INTERNATIONAL

A Division of North American Aviation, Inc.

NO. NAA-SR-MEMO-11225

DATE 4/5/65

PAGE 5 OF 9

II. METALLOGRAPHIC EXAMINATION OF P-ELEMENT SECTIONS

The N-type elements from T/E pumps DEV-4 and DEV-5 were left attached to the mounting structures. Only the P-elements were "potted" in plastic and sectioned. Each of these was cut in cross-section approximately through the center of the element stack-up. Then one side of each pump section was polished for examination. Thus the two P-type elements that were present in each pump were visible for inspection. One of these elements in a particular pump arbitrarily was designated as element No. 1 and the other as element No. 2.

Figures Number 1 and 2 show photomicrographs at a magnification of 250X of the appearance of typical areas in the cold side of the PbTe elements in these pumps. Element No.1 in Pump DEV-4 showed scarcely any contamination. The appearance in general was similar to that shown in the photomicrograph on the left in Figure 1. There was a little more contamination visible in element No. 2 than in element No. 1 in Pump DEV-4. The appearance of a typical area in element No. 2 is shown in the right hand photomicrograph in Figure 1. Areas typical of the appearance of elements No. 1 and No. 2 in Pump DEV-5 are shown in Figure 2. There appeared definitely to be more contamination in these elements that were performance tested for a longer period; but still rather insignificant compared to the massive contamination observed in the tin-containing type of P-elements. However, the greatest amount of contamination was observed in tin-containing P-type of elements which had been subjected to 2 or 3 times the length of performance testing that Pump DEV-5 received. In reviewing the published TDR-MEMO reports of examinations of T/E pumps containing the PbSnTe type of P-elements, Pumps 015 and 10-FSM-1 appeared to be the best for comparison. Pump 015 was performance tested at 1010°F for only 42 hours and yet there was a good deal more contamination found in the cold side of the P-elements than in Pump DEV-5. It is estimated that around 5 to 10 times as much contamination was observed in the P-elements from Pump 015 as in Pump DEV-5(2). Pump 10-FSM-1 was performance tested for approximately 2250 hours. It is estimated that the cold side of the P-elements in this pump showed around twice as much contamination as was observed in Pump DEV-5(3). It is not clear why Pump 015 showed more contamination after the short time performance tests than did Pump 10-FSM-1; but at any rate it appears from these observations that the tin-containing lead telluride material is more susceptible to contamination than the tin-free material.

DECLASSIFIED

ATOMICS INTERNATIONAL

A Division of North American Aviation, Inc.

NO. NA-SR-MEMO-11225

DATE 4/5/65

PAGE 6 OF 9

III. SUMMARY OF RESULTS

The P-elements from T/E Pumps DEV-4 and DEV-5 were cut out, mounted in Epoxy, and then polished cross-sections were examined for accumulation of contaminants in the cold side of the elements. Pump DEV-4 was run for 967 hours. Pump DEV-5 was tested for approximately 2160 hours. More contamination was found in Pump DEV-5 than in DEV-4; but it was estimated that the worst contamination visible in Pump DEV-5 was still significantly less than observed in pumps containing lead tin telluride elements and tested for comparable periods of time.

IV. CONCLUSIONS

Contaminants observed in the cold side of T/E pump elements fabricated with tin-free lead telluride P-materials were compared with T/E pump examinations of tin-containing, PbSnTe, elements. The results were not conclusive; however it appeared that there was significantly less contamination in the tin-free type of P-elements.

V. RECOMMENDATIONS

It is unfortunate that no data is available for the tin-free type of P-elements after 5000 to 6000 hours of performance testing. A comparison on this basis would be much more conclusive in comparing the extent of element poisoning, but no recommendations can be made under the current circumstances.

ATOMICS INTERNATIONAL

A Division of North American Aviation, Inc.

NO. ~~CONFIDENTIAL~~ NAA-SR-MEMO-11225

DATE 4/5/65

PAGE 7 OF 9

REFERENCES

1. a. Reed, E. L., "Microprobe and Metallographic Examination of SNAP 10A Pump Elements After Performance Tests," NAA-SR-TDR-9089 (10/30/63).
 - b. Reed, E. L., "Post Test Examination of SNAP 2 Thermo-electric Pump (Old Design)," NAA-SR-MEMO-9805, Page 24 (6/24/64).
 - c. Reed, E. L., N. H. Katz and others, "Fabrication and Post Test Evaluation of SNAP 10A Thermoelectric Pumps," NAA-SR-MEMO-9447, Page 200 (7/6/64).
 - d. Reed, E. L. and W. L. Cockrell, "Post Test Examination of SNAP 10A Thermoelectric Pump No. 015," NAA-SR-TDR-9711, Page 14 (4/8/64).
 - e. Reed, E. L., "Post Test Examination of T/E Pump FQ-3," NAA-SR-MEMO-10517, Page 25 (11/16/64).
2. Ibid. - (d).
3. Reed, E. L., "Post Test Examination of T/E Pump 10-FSM-1," NAA-SR-MEMO-10299, Page 29 (10/1/64).

~~CONFIDENTIAL~~
DECLASSIFIED

UNCLASSIFIED

ATOMIC INTERNATIONAL
A Division of North American Aviation, Inc.

~~CONFIDENTIAL~~

NO.

NAA-SR-MEMO-11225

DATE 4/5/65

PAGE 8 OF 9

P-Element No.1. (6030-1-1)

250X.

P-Element No.2. (6030-1-2)

250X.

Figure 1. Pump DEV-4. Cold Side of P-type PbTe Elements. Unetched.

719-P

~~CONFIDENTIAL~~
UNCLASSIFIED

UNCLASSIFIED

~~CONFIDENTIAL~~

NO. 11225

MEMO-11225

ATOMIC INTERNATIONAL

A Division of North American Aviation, Inc.

DATE

4/5/65

PAGE

9

OF

9

P-Element No.1. (6030-2-1)

250X.

P-Element No.2. (6030-2-2)

250X.

Figure-2. Pump DEV-5. Cold Side of P-type PbTe Elements. Unetched.