HEAVY SECTION STEEL TECHNOLOGY PROGRAM

5th

ANNUAL INFORMATION MEETING

MASTER

MARCH 25-26, 1971

Paper No. 19

U.S. ATOMIC ENERGY COMM.
ADVISORY COMMITTEE ON
REACTOR SAFEGUARDS

1971 MAR 19 PM 2 53

RECEIVED

AN ANALYTICAL BASIS FOR NOTCH SHARPENING
BY FATIGUE

J. G. Merkle
Oak Ridge National Laboratory
Oak Ridge, Tennessee

Sponsoring Program or Organization

HEAVY SECTION STEEL TECHNOLOGY PROGRAM

OAK RIDGE NATIONAL LABORATORY

OPERATED BY UNION CARBIDE CORPORATION • FOR THE U.S. ATOMIC ENERGY COMMISSION

AN ANALYTICAL BASIS FOR NOTCH
SHARPENING BY FATIGUE*

J. G. Merkle

Oak Ridge National Laboratory
Oak Ridge, Tennessee

ABSTRACT

An important problem in the design of large fracture test specimens is the development of a practical and reliable method for sharpening the machined notches that are used to cause fracture. While gross load cycling does not appear to be a feasible method for notch sharpening by fatigue, for large specimens, local load cycling does appear to be a feasible method. Local compressive stresses, applied to the notch faces only, for example by hydraulic pressure, can produce the same crack tip stress intensity factor that would be produced by an overall tensile stress of the same magnitude. Calculations are made to estimate the number of load cycles required to initiate flaw growth by fatigue, at the base of a machined notch, and the number of load cycles required to grow the flaw a given distance by fatigue. Experimental data have been obtained, which tend to verify the analysis and to support the feasibility of notch sharpening by fatigue, using locally applied loads.

* Research sponsored by the U.S. Atomic Energy Commission in support of the Heavy Section Steel Technology (HSST) Program under contract with the Union Carbide Corporation.

NOTICE

This report was prepared as an account of work sponsored by the United States Government. Neither the United States nor the United States Atomic Energy Commission, nor any of their employees, nor any of their contractors, subcontractors, or their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness or usefulness of any information, apparatus, product or process disclosed, or represents that its use would not infringe privately owned rights.

NOMENCLATURE

a	Defect size, generally half-length, in.
a ₀	Initial defect size, generally half length, in.
b	Half the surface length of a part-through surface flaw, in.
C	Fracture Mechanics shape factor, dimensionless
C'	Notch tip stress concentration shape factor, dimensionless
C _F	Flaw growth rate coefficient; for dimensions see Eq. (31)
E	Modulus of elasticity, psi
e	Nominal strain, in./in.
K _I	The elastic crack-tip stress intensity factor for plane strain conditions, ksi·in. ^{1/2}
K _{Ic}	Critical value of the elastic crack-tip stress intensity factor for static plane strain conditions, ksi·in. ^{1/2}
K _F	Fatigue strength reduction factor, dimensionless
K _m	Modified stress concentration factor for fatigue, dimensionless
K _t	Theoretical elastic stress concentration factor, dimensionless
K _ε	Actual strain concentration factor, dimensionless
K _σ	Actual stress concentration factor, dimensionless
k	An exponent, dimensionless
N	Number of load cycles, dimensionless
N _i	Number of load cycles required to initiate flaw growth by fatigue, dimensionless
N _p	Number of load cycles required to propagate a flaw a given distance by fatigue, dimensionless
n	An exponent, dimensionless
q	Notch sensitivity factor, dimensionless

S	Nominal stress, ksi
S'_{ult}	Nominal ultimate strength, ksi
ϵ	Actual strain at the root of a notch, in./in.
ϵ^E	Elastic strain, in./in.
ϵ^P	Plastic strain, in./in.
ρ	Root radius of a notch, in.
σ	Actual stress at the root of a notch, ksi
ϕ	A characteristic dimension that varies with ultimate strength and that influences the notch sensitivity of a material, in.

FIGURE CAPTIONS

- Fig. 1. Variation of the Notch Sensitivity Factor with Notch Root Radius, for a Quenched and Tempered Steel (from Ref. 5).
- Fig. 2. Variation of the Characteristic Dimension ϕ with Ultimate Strength, for Steels (from Ref. 12).
- Fig. 3. Assumed Loading Branch of the Cyclic Stress-Strain Curve for A 533-B, Class 1 Steel.
- Fig. 4. An Example Hysteresis Curve for A 533-B, Class 1 Steel.
- Fig. 5. Plot of Total Strain Range versus the Function $(\Delta\sigma / E)^{1/2}$
- Fig. 6. Total Strain Range versus Cyclic Life for Many Materials (from Ref. 15).
- Fig. 7. Graphical Comparison Between Experimental Data and Two Empirical Equations for Calculating the Notch Sensitivity Factor as a Function of Notch Root Radius and Ultimate Tensile Strength.
- Fig. 8. Variation of the Notch Sensitivity Factor, and the Number of Cycles Required for the Initiation of Fatigue Crack Growth with the Range of Variation of the Stress Intensity Factor.
- Fig. 9. Delay Effects in Fatigue Crack Growth Due to Reduction of the Cyclic Stress Range from σ_1 to σ_2 in Aluminum Alloy 7075-76 (from Ref. 19).
- Fig. 10. Dimensions of the HSST Program Intermediate Tensile Test Specimen.
- Fig. 11. Fracture Surface of the 1/6-Scale Model Tensile Specimen, Showing the Fatigue Sharpened Flaw (Southwest Research Institute photograph).
- Fig. 12. Fracture Surface of the Intermediate Tensile Test Specimen Tested at +50°F, Showing the Fatigue Sharpened Flaw (Southwest Research Institute photograph).
- Fig. 13. Fracture Surface of the Intermediate Tensile Test Specimen Tested at +100°F, Showing the Fatigue Sharpened Flaw (Southwest Research Institute Photograph).

INTRODUCTION

An important problem in the design of the large fracture test specimens for the HSST program is the development of a method for sharpening the machined notches, especially for the specimens that are to be tested in the frangible range. Some consideration has been given to sharpening the notches by fatigue, using gross load cycling. However, a completely satisfactory method for calculating the number of load cycles required to initiate crack growth by fatigue has not been available. Nevertheless, the calculations that have been made to date indicate that gross load cycling would probably be impractical.

The purpose of this report is twofold. First, a method is proposed for estimating the number of load cycles required to initiate flaw growth by fatigue, based on a recent paper by Topper, Wetzel and Morrow.^{1*} Secondly, it is suggested that fatigue notch sharpening can be accomplished by applying local cyclic loads to the notch faces, with no other loads acting on the structure. This technique has been used successfully by the Westinghouse Electric Corporation in the fatigue precracking of their spin rotor specimens.²

BACKGROUND

The sharpening of a machined notch by fatigue takes place in three phases: (1) the initiation of a fatigue flaw at the base of the machined notch; (2) a delay in the growth of the flaw due to a reduction in the cyclic load level, if any; and (3) the growth of the flaw by fatigue

*Superscripts refer to the references given at the end of the paper.

under cyclic load. Methods are available to calculate the number of load cycles corresponding to phases (2) and (3). However, a universally accepted method is not available for calculating the number of load cycles required to accomplish phase (1). It is important to have an estimate of the number of load cycles corresponding to all three phases, so that the feasibility of local load cycling can be evaluated and the importance of such variables as the notch root radius and the cyclic load level can be determined.

To calculate the number of load cycles required to initiate flaw growth by fatigue at the base of a machined notch, it will be assumed that this number of load cycles is determined by the actual total strain range at the root of the notch.¹ It will also be assumed that this number of load cycles can be determined from the same relationship that governs the low cycle fatigue of unnotched specimens.¹ The basic problem is therefore the stress analysis problem of estimating the cyclic total strain range at the base of a notch. Since this problem involves cyclic plasticity, there is no exact solution and an empirical approach must be taken. One approach to this type of problem is to bypass the calculation of the notch tip strains altogether, and to instead calculate, directly from experimental data, a factor called the fatigue strength reduction factor,³ which is defined as the ratio of the total strain range to failure in a given number of cycles for a smooth laboratory specimen, and the total nominal strain range to failure in the same number of cycles for a given structure. It is well known^{4,5} that experiments have shown that this factor, labeled K_f , has a value equal to or less than the value of the theoretical elastic stress concentration

factor, K_t . One hypothesis for explaining this phenomenon is that the cyclic total strain range that governs crack initiation is not the total strain range at the exact root of the notch, but rather the cyclic total strain range at a small distance ahead of the notch root.⁶ Calculations based on this hypothesis, and on Neuber's elastic notch tip stress equations,⁷ have been made,⁶ but they do not consider the actual cyclic yielding that occurs near the tip of the notch. The approach to be used in this report will consider the cyclic yielding that occurs near the root of the notch, by the method of calculation suggested by Topper et al.¹

A problem closely related to the calculation of notch tip strains is the calculation of the theoretical elastic stress concentration factor, K_t , to which the notch tip strains must be related. Neuber's equations⁷ do not cover the case of a semi-elliptical part-through surface crack, which is one of the shapes of interest in this report, nor do they cover the Compact Tension specimen, on which a considerable amount of the fatigue data for A 533-B steel have been obtained. Thus, it is necessary to find a way of calculating the elastic stress concentration factor, K_t , for both a semi-elliptical part-through surface notch and a Compact Tension specimen. Fortunately, as will be shown, this method already exists.

DESCRIPTION OF THE ANALYTICAL METHOD

Based on Neuber's work,⁷ Topper et al.¹ suggested that the actual cyclic stress and strain concentration factors, K_σ and K_ϵ , could be related by the equation

$$(K_\sigma K_\epsilon)^{1/2} = K_m, \quad (1)$$

where K_m will be called the modified stress concentration factor for fatigue. This term was labeled K_f , and called the fatigue concentration factor in Ref. 1. However, the term K_f has already been used to denote the fatigue strength reduction factor,³ and thus a change in nomenclature seems in order. The terms K_f and K_m may sometimes be nearly equal numerically, but their definitions are nevertheless different.

The factors K_σ and K_ϵ are defined by the equations

$$K_\sigma = \frac{\Delta\sigma}{\Delta S}, \quad (2)$$

and

$$K_\epsilon = \frac{\Delta\epsilon}{\Delta e}, \quad (3)$$

where σ and S represent the maximum (notch root) and the nominal stresses, respectively, and ϵ and e represent the maximum and the nominal strains, respectively. For cycling in the nominal elastic range,

$$\Delta e = \frac{\Delta S}{E}, \quad (4)$$

and substituting Eq. (4) into Eq. (3) gives

$$K_\epsilon = \frac{E\Delta\epsilon}{\Delta S}. \quad (5)$$

Substituting Eqs. (2) and (5) into Eq. (1) and rearranging, gives,

$$(\Delta\sigma \Delta\epsilon E)^{1/2} = K_m \Delta S \quad . \quad (6)$$

The factors $\Delta\sigma$ and $\Delta\epsilon$ are assumed to be the coordinates of a point on the uniaxial cyclic stress-strain curve. Thus, if a value of $K_m \Delta S$ is specified, it determines a value of $\Delta\epsilon$, the cyclic total strain range at the notch root. A specified value of $\Delta\epsilon$ will, in turn, determine the number of load cycles required to initiate crack growth by fatigue. This number of load cycles will be designated by the symbol N_i .

CALCULATION OF THE ELASTIC STRESS CONCENTRATION FACTOR

Since Neuber's equations⁷ do not cover the cases of a semi-elliptical part-through surface notch in a rectangular tension bar, or the Compact Tension specimen, another method must be found for calculating K_t for these shapes. Fortunately, this calculation can be made by rearranging an equation suggested by Irwin et al.⁸

$$K_I = \lim_{\rho \rightarrow 0} \frac{1}{2} K_t S \sqrt{\pi \rho} \quad , \quad (7)$$

where K_I is the linear elastic fracture mechanics stress intensity factor, in $\text{ksi}\cdot\text{in.}^{1/2}$, and ρ is the notch root radius, in in. Although an attempt has been made⁹ to establish the generality of Eq. (7), a completely general derivation of Eq. (7) still does not exist.¹⁰ Nevertheless, according to Irwin,¹⁰ its use has been justified by experience, and it will therefore be used for this analysis.

It can be shown from Neuber's equations that

$$\lim_{\rho \rightarrow 0} K_t = C' \sqrt{\frac{a}{\rho}} , \quad (8)$$

where C' is a dimensionless coefficient, and a is the notch depth, in in. (Note that Neuber⁷ uses the symbol t for the depth of a shallow notch, and the symbol a for the thickness of the remaining ligament beyond a deep notch.)

From Eq. (8), it is evident that

$$\lim_{\rho \rightarrow 0} K_t \sqrt{\rho} = C' \sqrt{a} . \quad (9)$$

Combining Eqs. (9) and (7) gives

$$K_I = \frac{1}{2} S C' \sqrt{\pi a} . \quad (10)$$

The basic equation of fracture mechanics is

$$K_I = C S \sqrt{\pi a} , \quad (11)$$

where C is the fracture mechanics "shape" factor. By equating the right hand sides of Eqs. (10) and (11)

$$C' = 2 C . \quad (12)$$

Therefore, in Eq. (8), for small values of ρ (or large values of a/ρ),

$$K_t = 2 C \sqrt{\frac{a}{\rho}} . \quad (13)$$

Also, for the same conditions, and replacing K_I by ΔK_I , and S by ΔS , Eq. (7) can be rearranged to read

$$K_t \Delta S = \frac{2(\Delta K_I)}{\sqrt{\pi \rho}} . \quad (14)$$

Thus, if a fracture mechanics stress intensity factor solution is available for a particular loading and geometry case, then the stress concentration factor, and the elastically calculated maximum stress, can be obtained for the same case, for any specified, but small root radius. The converse is also true.

THE MODIFIED STRESS CONCENTRATION FACTOR FOR FATIGUE AND THE NOTCH SENSITIVITY FACTOR

Whereas the elastic stress concentration factor, K_t , can be calculated from theory, the ratio of K_m to K_t will be considered empirical. The empirical relationship between K_m and K_t will be assumed to have the form^{1,4,5}

$$K_m = 1 + q (K_t - 1) , \quad (15)$$

where q is called the notch sensitivity factor, and has a value of between zero and unity. An expression of the same form is commonly used to relate the fatigue strength reduction factor K_f to the elastic stress concentration factor K_t .⁴ In the following discussion, it will be assumed that the notch sensitivity factor q can be used to calculate both K_f and K_m . This is tantamount to assuming that K_f and K_m have nearly equal numerical values. Experimentally, q is found to be a function mainly of the notch root radius, ρ , and of the material tensile strength, S'_{ult} . A plot of the notch sensitivity factor, q , versus the root radius, ρ , for a quenched and tempered steel⁵ is shown in Fig. 1. Notice that q decreases as the root radius decreases. A general form

of an empirical equation for q is

$$q = \frac{1}{1 + \left(\frac{\varphi}{\rho}\right)^k}, \quad (16)$$

where φ is a characteristic dimension that depends on the tensile strength of the material, in in., and k is an exponent. Langer⁴ and Topper et al.¹ suggest that $k = 1$, and for $k = 1$, Bickell and Ruiz¹¹ suggest the following relationship between φ and S'_{ult} ,

$$\varphi = 10^{-\left(\frac{255 - S'_{ult}}{165}\right)}. \quad (17)$$

In Eq. (17), S'_{ult} is expressed in ksi. On the other hand, Tetelman and McEvily¹² suggest that, for steels, $k = 1/2$, and that $\varphi^{1/2}$ can be determined from the curve shown in Fig. 2. Later on, both forms of Eq. (16) will be compared with experimental data. Before doing this, however, it is necessary to define a method for estimating the shape of the cyclic stress-strain curve, for cases where this curve has not been determined experimentally.

AN ESTIMATE OF THE SHAPE OF THE CYCLIC STRESS-STRAIN CURVE

The tensile stress-strain curve of A533-B steel, at room temperature,¹³ is shown in Fig. 3. On first loading, the material exhibits a "yield plateau" which extends, at the yield stress level, from the yield strain to a strain of about 1.3%. However, the yield plateau of a structural steel is usually eliminated by cycling, so it will be assumed that the loading branch of the cyclic stress strain curve is the loading branch of the virgin stress-strain curve, but with the strain hardening branch extrapolated backwards to its intersection with the linear elastic branch. It will also be assumed that the unloading branch of the cyclic stress-strain curve (i.e., that part that occurs when the stress is decreasing toward zero) is linear, with a slope equal to the modulus of elasticity. These assumptions are sufficient to define a cyclic stress-strain curve, for any specified value of the/ ^{cyclic strain range.} An example cyclic stress-strain curve, for A533-B steel, is shown in Fig. 4. It is also possible to define the quantities $\Delta\sigma$ and $\Delta\epsilon$ in terms of the values of σ and ϵ for a point on the loading branch of the cyclic stress-strain curve. Referring to Fig. 4 if the stress range, $\Delta\sigma$, is equal to 2σ , then the range of strain, $\Delta\epsilon$, is given by

$$\Delta\epsilon = 2\epsilon^E + \epsilon^P, \quad (18)$$

where ϵ^E and ϵ^P are the elastic and the plastic strains, respectively, that occur during loading to the stress σ . Using the definition of total strain,

$$\epsilon = \epsilon^E + \epsilon^P, \quad (19)$$

Eq. (18) can be rewritten to read

$$\Delta\epsilon = \epsilon^E + \epsilon, \quad (20)$$

and finally,

$$\Delta \epsilon = \frac{\sigma}{E} + \epsilon \quad . \quad (21)$$

The value of the quantity $(\Delta \sigma \Delta \epsilon E)^{1/2}$, corresponding to a given value of $\Delta \epsilon$, is then determined from the following equation:

$$(\Delta \sigma \Delta \epsilon E)^{1/2} = \Delta \sigma \left[\frac{\Delta \epsilon E}{\Delta \sigma} \right]^{1/2} . \quad (22)$$

Since

$$\Delta \sigma = 2\sigma \quad , \quad (23)$$

$$(\Delta \sigma \Delta \epsilon E)^{1/2} = 2\sigma \left[\frac{\Delta \epsilon E}{2\sigma} \right]^{1/2} . \quad (24)$$

Table 1 contains a series of calculations, made according to Eqs. (21) and (24), for A533-B steel, using Fig. 3.

Table 1. Values of the Cyclic Strain, $\Delta \epsilon$, and the Parameter $(\Delta \sigma \Delta \epsilon E)^{1/2}$, for Specified Values of the Stress σ , which Equals $\Delta \sigma/2$

σ (ksi)	ϵ (%)	σ/E (%)	$\Delta \epsilon$ (%)	$(\Delta \sigma \Delta \epsilon E)^{1/2}$ (ksi)
55	0.18	0.18	0.36	110
58	0.51	0.19	0.70	156
60	0.65	0.20	0.85	175
65	1.12	0.22	1.34	228
70	1.65	0.23	1.88	281

A curve of $\Delta \epsilon$ versus $(\Delta \sigma \Delta \epsilon E)^{1/2}$ is plotted in Fig. 5.

CALCULATIONS OF NOTCH SENSITIVITY FACTORS FROM EXPERIMENTAL DATA

The preceeding discussion has provided a method by which notch sensitivity factors can be calculated from experimental data. Therefore, in this section, three sets of notch sensitivity values will be calculated from experimental data and the results will be compared with the predictions of Eq. (16), in order to ascertain the probable accuracy with which estimates of q can be made for values of ρ other than those for which data exist. For purposes of plotting, Eq. (16) is rearranged to read,

$$\log\left(\frac{1}{q} - 1\right) = \log(\varphi)^k - k \log \rho, \quad (25)$$

which is a straight line on log-log paper.

The first set of data⁵ is that shown plotted in Fig. 1. Values of q can be scaled directly from Fig. 1. The results are given in Table 2.

Table 2. Notch Sensitivity Values
Scaled From the Data Points Shown
Plotted in Figure 1

ρ (in.)	q	$\frac{1}{q} - 1$
0.0005	0.05, 0.11	19, 8.1
0.0010	0.175, 0.185	4.71, 4.4
0.0015	0.33	2.0
0.025	0.78	0.28
0.033	0.90	0.11

The second set of data for which notch sensitivity factors can be calculated was obtained, with A533-B steel, by the Westinghouse Electric Corporation in the process of fatigue precracking some of the Compact Tension specimens tested in support of the Heavy Section Steel Technology Program.¹⁴ The fatigue precracking data are given in Table 3.

Table 3. Data on the Number of Load Cycles Required to Initiate Crack Growth in A533-B Steel

Specimen	ΔK_I (ksi./ $\sqrt{\text{in.}}$)	Number of Cycles to Initiation of Crack Growth ($\times 10^{-3}$)
6T Compact Tension	30	52, 69, 31, 113, 77, 41, 149, 84;
10T Compact Tension	52.5	34, 13, 18, 15, 193

The root radius of the machined notches in these specimens was 0.003 in.¹⁴ Thus, from Eq. (14), the values of $K_t \Delta S$ for these specimens were 615 ksi for the 6T specimens, and 1076 ksi for the 10T specimens. For large values of K_t , Eq. (15) can be approximated by the expression

$$K_m \sim q K_t, \quad (26)$$

from which it follows that

$$K_m \Delta S = q (K_t \Delta S), \quad (27)$$

and

$$q = \frac{K_m \Delta S}{K_t \Delta S}. \quad (28)$$

If N_i , the number of cycles to the initiation of fatigue crack growth, is known then $\Delta \epsilon$, the total strain range, can be determined directly from a curve of $\Delta \epsilon$ versus N_i . For this purpose, the fatigue curve plotted by Manson,¹⁵ for several different materials, will be used. This curve is shown in Figure 6. Once $\Delta \epsilon$ is known, from Figure 6, then $K_m \Delta S$ can be determined from Figure 5. Eq. (28) can then be used to calculate the value of q . The results of such a series of calculations, for the Westinghouse specimens, are given in Table 4.

Table 4. Calculated Notch Sensitivity Factors
for Some HSST Program Compact Tension
Specimens Tested by Westinghouse

N_i (Cycles)	$\Delta\epsilon$ (%)	$K_m \Delta S$ (ksi)	q	$\frac{1}{q} - 1$	Remarks
6T Compact K_{Ic} Specimens					
31,000	0.74	163	0.265	2.77	Minimum N_i
60,000	0.69	156	0.254	2.94	Mode N_i
149,000	0.60	145	0.236	3.24	Maximum N_i
10T Compact K_{Ic} Specimens					
13,000	0.90	181	0.168	4.95	Minimum N_i
18,000	0.82	171	0.159	5.30	Mode N_i
193,000	0.55	137	0.127	6.88	Maximum N_i

The third set of data that furnish notch sensitivity values are of a set/fatigue crack growth rate data from 0.40-in. through-cracked plates and 1.0-in. part-through cracked specimens, of A302-B, and A508 steel that were tested by Mowbray, Andrews and Brothers.¹⁶ The calculations for these specimens are given in Table 5. For purposes of these calculations, the cyclic stress-strain curves for A302-B and A508-2 steels have been assumed to be the same as that for A533-B steel.

A comparison between experimental data, interpreted by the method of this report, and the predictions of Eqs. (16) and (25) can now be made. This comparison is made graphically in Fig. 7. The two straight lines in Fig. 7 represent the equations suggested by References 11 and 12. Reference 11 suggests that in Eq. (25), $k = 1$, and from Eq. (17), using $S'_{ult} = 87$ ksi, $\phi = 0.0084$ in. Reference 12 suggests that in Eq. (25), $k = 1/2$, and from Fig. 2, again using $S'_{ult} = 87$ ksi, $\phi^{1/2} = 0.07$ in.^{1/2}.

Table 5. Calculated Notch Sensitivity Factors for Some Through-Cracked and Part-Through Cracked Specimens of A302-B and A508-2 Steel

a (in.)	B (in.)	Type of Crack	Material	ρ (in.)	ΔK (ksi./in.)	$K_t \Delta S$ (ksi)	N_1 (cycles)	$\Delta \epsilon$ (%)	$K_m \Delta S$ (ksi)	q	$\left(\frac{1}{q} - 1\right)$
0.188	0.4	Through Crack	A302-B	0.0035	50	953	1000	1.8	272	0.286	2.50
0.188	0.4	Through Crack	A302-B	0.0035	40	761	1800	1.4	230	0.302	2.31
0.188	0.4	Through Crack	A508-2	0.0035	45	857	1000	1.8	272	0.318	2.14
0.188	0.4	Through Crack	A508-2	0.0035	58	1105	5200	1.1	200	0.181	4.52
0.100	1.0	Part-Through Crack	A302-B	0.003	35	718	5000	1.1	200	0.278	2.60

From Figure 7, it can be seen that most of the data for small root radii ($\rho < 0.015$ in.) fall between the lines for the two equations, and that the line for $k = 1$ seems to give a better overall fit to the data than the line for $k = 1/2$. However, at a root radius of 0.015 in., which is near that contemplated for at least some of the HSST Program intermediate tensile test specimens, there is almost no difference between the predictions of the two equations, because their curves cross at about $\rho = 0.015$ in. One matter does need further clarification, and that is the existence of two data points, one at $\rho = 0.003$ in., and the other at $\rho = 0.0035$ in. that are noticeably above the $k = 1$ line. An explanation for this phenomenon can be obtained from Figure 8, which shows that the notch sensitivity factor is actually a function of the cyclic stress intensity factor. At $\Delta K = 50 \text{ ksi}\cdot\text{in.}^{1/2}$ q suddenly decreases, causing a reduction in the cyclic total strain range at the notch root, and a consequent increase in the number of cycles to the initiation of fatigue crack growth. Based on Figure 8, the maximum value of ΔK that should be used for initiating fatigue crack growth in HSST intermediate fracture test specimens is $40 \text{ ksi}\cdot\text{in.}^{1/2}$. Fortunately, this limit coincides with the limit currently prescribed by the ASTM specification that governs K_{Ic} testing,¹⁷ as explained below. Paragraph 6.5.2 of Ref. 17 specifies that the value of ΔK_I to be used for producing the last 2 1/2% of overall crack length shall meet the requirement that

$$\Delta K_I \leq 0.0012 E \quad , \quad (29)$$

where E is the modulus of elasticity of the material. For steel, Eq. (29) limits the value of ΔK_I , for the last 2 1/2% of overall crack length, to

36 ksi·in.^{1/2}. Paragraph 6.5.3 of Ref. 17 further specifies that the maximum stress intensity factor used for fatigue precracking, designated $K_{I(max)}$, shall meet the requirement that

$$\Delta K_I \geq 0.9 K_{I(max)} \quad (30)$$

For $\Delta K_I = 36$ ksi·in.^{1/2}, Eq. (30) determines a value of $K_{I(max)}$ of 40 ksi·in.^{1/2}

On the basis of Figs. 7 and 8, it is recommended that fatigue crack growth be initiated by using a ΔK_I of 40 ksi·in.^{1/2}, and that q be estimated from Figure 7, using the curve for $k = 1$. It is also recommended that actual fatigue precracking data be obtained, on fracture test specimens, using the approximate crack length and the actual root radius to be used in the intermediate test specimens.

METHOD FOR ESTIMATING THE NUMBER OF CYCLES DELAY CAUSED BY A REDUCTION IN THE CYCLIC LOAD

It has been found experimentally, using aluminum, that reducing the cyclic load level causes a crack that has been growing in fatigue to stop growing, for a certain number of cycles.^{18,19} The number of cycles delay depends upon the percent reduction in the cyclic load level, as shown in Figure 9. Figure 9 shows that the number of cycles delay caused by a ten percent reduction in the cyclic load level is less than 100, which, for the purposes of this report, is negligible. Therefore, unless the load drop exceeds 10%, the number of load cycles delay will be neglected in the remainder of this report.

CRACK GROWTH RATE CALCULATIONS BASED ON THE FRACTURE MECHANICS APPROACH

The rate of growth of cracks by fatigue in HSST Program material (A533-B steel) can be described by the equation,²⁰

$$\frac{da}{dN} = C_F (\Delta K_I)^n, \quad (31)$$

where da/dN = the crack growth rate, in in. per cycle; K_I = the Mode I stress intensity factor, in $\text{ksi} \cdot \text{in.}^{1/2}$; and C_F and n are constants to be determined by test.

Reference 20 suggests that the value of C_F may be taken as 10^{-9} inches per cycle, per $(\Delta K_I)^n$, and that the value of n may be taken as 2.5. These values will be used for subsequent calculations.

FATIGUE PRECRACKING CALCULATIONS FOR A PART-THROUGH NOTCH IN AN INTERMEDIATE TENSILE TEST SPECIMEN

A calculation will now be made of the number of load cycles required to initiate fatigue crack growth at the base of a machined ^{part-through} notch in an intermediate tensile test specimen, and the number of load cycles required to then propagate that crack a certain distance. The following values will be assumed:

$\Delta K_I = 40 \text{ ksi} \cdot \text{in.}^{1/2}$, for initiation;

$\Delta K_I = 36 \text{ ksi} \cdot \text{in.}^{1/2}$, for propagation;

$\rho = 0.015 \text{ in.}$, the root radius;

$a_0 = 2.25 \text{ in.}$, the initial notch depth;

$C = 0.9$, the shape factor;

$\frac{a}{2b} = 0.36$, the crack shape ratio (the ratio of the crack depth to the total surface length).

Using Eq. (14),

$$K_t \Delta S = \frac{(2)(40)}{\sqrt{(\pi)(0.015)}} = 367 \text{ ksi} .$$

From Figure 7, for $\rho = 0.015$ in.,

$$\frac{1}{q} - 1 = 0.58 \text{ so that } q = 0.632.$$

Using Eq. (27)

$$K_m \Delta S = (0.632)(367) = 232 \text{ ksi}.$$

From Figure 5,

$$\Delta \epsilon = 1.37\%.$$

Finally, from Fig. 6,

$$N_i = 2000 \text{ cycles}.$$

The number of load cycles required to initiate flaw growth by fatigue is estimated to be 2000 cycles.

The number of load cycles delay caused by a reduction of the ΔK_I level from $40 \text{ ksi}\cdot\text{in.}^{1/2}$ to $36 \text{ ksi}\cdot\text{in.}^{1/2}$ is assumed to be negligible.

Reference 17 requires that Δa be not less than 0.05 a. In other words

$$\Delta a = 0.05 (a_o + \Delta a) . \quad (32)$$

Therefore,

$$\begin{aligned} 0.95 \Delta a &= 0.05 a_o \\ \Delta a &= 0.0526 a_o . \end{aligned} \quad (33)$$

From Eq. (33),

$$\Delta a = (0.0526)(2.25) = 0.118 \text{ in.}$$

Eq. (31) can be rewritten in the form

$$N_p = \frac{\Delta a}{C_F (\Delta K_I)^n} , \quad (34)$$

where N_p is the number of load cycles required to propagate a crack a

distance Δa at a constant ΔK_I level. Using Eq. (34),

$$\begin{aligned} N_P &= \frac{1.18 \times 10^{-1}}{(10^{-9})(36)^{2.6}} \\ &= \frac{1.18 \times 10^8}{7.8 \times 10^3} \end{aligned}$$

$$N_P = 0.151 \times 10^6 = 15,100 \text{ cycles.}$$

Rounding off, $N_P \sim 15,000$ cycles.

The number of load cycles required to propagate the crack the required distance is about 15,000 load cycles. Thus, ^{in this case} the propagation phase takes considerably longer than the initiation phase. This is fortunate since the estimate of the number of load cycles required to initiate flaw growth by fatigue is probably less accurate than the estimate of the number of load cycles required for propagation. As an approximation we can say that notch sharpening by fatigue will require about 20,000 load cycles.

The fact that fatigue flaw growth can be initiated, in a reasonable number of cycles, from a machined notch with a root radius as large as 0.015 in. is of practical importance because it means that the machining of the notch should not be too difficult. In fact, by calculating the maximum value of K_m as a function of ρ , it can be shown that there is very little to be gained by reducing the notch root radius below 0.015 in.

FEASIBILITY OF APPLYING LOCAL CYCLIC LOADS TO THE CRACK FACES

It is generally agreed that it would be impractical to sharpen a machined notch in either a large tensile test specimen or a test pressure

vessel by cycling the total load on the specimen. However, it is also possible to produce the same stress intensity factor at the crack tip that would be produced by the overall load by applying, to the crack faces only, the negative of the stress distribution that would exist over the crack area if the crack was not present. This is the principle applied by the Westinghouse Electric Corporation when they fatigue pre-crack their spin burst specimens by means of cyclic fluid pressure in a hole from which a slot has been machined.² In the case of a spin burst specimen, only the ends of the hole and of the crack have to be sealed against fluid pressure, and there is no other access to the crack during cycling. In the case of a part-through surface notched specimen, the entire surface entrance to the crack would have to be sealed against pressure. Thus, pressure cycling would be more difficult for the part-through surface notched specimen than it is for the spin rotor specimen.

To estimate the magnitude of the cyclic pressure that would have to be applied to the crack faces, Eq. (11) is rearranged to read

$$\Delta S = \frac{\Delta K_I}{C\sqrt{\pi a}} \quad (35)$$

Using the values of $\Delta K_I = 40 \text{ ksi}\cdot\text{in.}^{1/2}$, $C = 0.9$ and $a = 2.25$, the calculated value of ΔS is

$$\Delta S = \frac{40}{(0.9)(2.65)} = 16.8 \text{ ksi} \quad .$$

Based on this calculation of cyclic pressure, Kooistra²¹ has estimated that it is feasible to seal the entrance to a part-through surface notch in

the body of an intermediate test vessel, or in an intermediate tensile specimen, by means of a steel sealing block pressed against the face of the test specimen. For effective sealing, the contact surfaces of the sealing block, and of the specimen, should be machined flat and polished to a smooth finish. The sealing block should be provided with an O-ring that surrounds the entrance to the machined notch and defines the area on the sealing block over which the hydraulic pressure acts. The sealing block would have a drilled passage through which the hydraulic pressure reaches the notch cavity.²¹ Such a pressure sealing device has been built by Derby and Abbatiello at ORNL, and the results of this development will be reported separately.

EXPERIMENTAL VERIFICATION OF THE ANALYSIS USING A PART- THROUGH SURFACE NOTCHED SPECIMEN FATIGUED IN BENDING

An important part of the HSST program is the testing of a series of large tensile specimens containing part-through surface flaws. As shown in Fig. 10, these tensile specimens have a cross section measuring 6 in. by 18 in., and they contain a part-through surface flaw measuring about 2.25 in. deep and about 7.0 in. long on the surface.²² These tensile specimens are known as the intermediate tensile test specimens, because they are intermediate in size between standard laboratory specimens and the full scale wall thicknesses of the currently largest nuclear pressure vessels. For testing at temperatures below the "upper shelf" temperature, it is necessary for the flaws in fracture test specimens to have sharp leading edges in order for the test results to be meaningful. Lack of notch sharpness leads to artificially high values of apparent fracture toughness.

As shown in Fig. 10, the machined notches in the intermediate tensile test specimens have root radii of about .015 in., which is within the range of root radii that ^{appear to be} suitable for notch sharpening by fatigue. Also, the length and thickness of the specimen, and the depth of the flaw, are such that a cyclically applied transverse bending load at midspan, of reasonable magnitude, is sufficient to produce a ΔK_I of about $40 \text{ ksi} \cdot \text{in.}^{1/2}$ at the tip of the flaw.²³ Thus a method exists for checking the validity of the calculations described in this report without the necessity of first building a complicated device for applying the cyclic load. It should also be noted that the notches in other part-through cracked tensile specimens have already been fatigue sharpened in bending.^{24,25}

Before applying the bending fatigue procedure to a full scale 6-in.-thick intermediate tensile test specimen, it was decided to apply the same procedure to a 1/6-scale model specimen. If the procedure worked for the 1/6-scale model specimen, then presumably it would work for the full 6-in.-thick tensile specimen.

The flaw design chosen for the specimens to be tested is a part-circular surface crack which, for the 6-in.-thick tensile specimen, has a maximum depth of two in. and a surface length of eight in. The part-circular surface flaw was chosen because its shape is close to the shape of flaws that have occurred naturally, and because it is easier and cheaper to machine than the semi-elliptical flaws that were used for previous intermediate tensile test specimens.²¹ Stress intensity factor analyses for the part-circular surface flaw, for both a uniform nominal stress and for pure bending, have been obtained by Smith and Alavi.²⁶ Using these solutions, it was determined that transverse bending loads of 187,000 pounds and 12,700 pounds, on the six-in.-thick specimen and on the one-in.-thick specimen respectively, would produce ΔK_I values of $36 \text{ ksi} \cdot \text{in.}^{1/2}$ at the mid-depth point and $49.3 \text{ ksi} \cdot \text{in.}^{1/2}$ at the surface intersection points. This was considered an acceptable range for fatigue precracking.

The 1/6-scale model was tested first.²⁷ After 15,000 cycles of load, visual examination indicated that fatigue crack growth had commenced. After a total of 25,000 load cycles, the specimen was broken in tension, revealing the fatigue-sharpened flaw shown in Fig. 11. For the 6-in.-thick tensile specimen tested next, fatigue crack growth had

commenced at 15,000 cycles of load, and a total of 35,000 load cycles was applied to the specimen before testing it to failure in tension at +50°F. The specimen failed at an average stress on the uncracked section about equal to the yield stress, revealing the fatigue sharpened flaw shown in Fig. 12.²⁷ A second 6-in.-thick tensile specimen was then fatigue precracked in bending and tested to failure in tension at +100°F. In this specimen, fatigue crack growth had commenced at 15,000 load cycles, and a total of 46,000 load cycles was applied to the specimen. The specimen failed in the tension test by necking on the plane of the crack. The failure surface, and the fatigue sharpened portion of the flaw, are shown in Fig. 13.²⁷ Our successful experience with these three specimens is considered *prima facie* evidence of the usefulness of the methods of calculation described in this report. The observed number of load cycles required to initiate fatigue crack growth is greater than the estimated number of load cycles, but not by enough to reduce the feasibility of notch sharpening by fatigue.

CONCLUSIONS AND RECOMMENDATIONS

1. A relationship exists between the fracture mechanics shape factor for a crack and the stress concentration shape factor for a sharp notch, such that the stress concentration factor for a sharp notch can be calculated if the fracture mechanics stress intensity factor is known for a crack of the same shape. The converse is also true.
2. A method is developed for estimating the shape of the uniaxial cyclic stress-strain curve. Such an estimate, or actual data, are needed for calculating the total strain range at the root of a notch under cyclic loading.
3. An existing method of analysis is used to calculate notch sensitivity factors from three sets of experimental data, one of which is for A533-B steel. These calculations show that notch sensitivity factors can be estimated with existing empirical equations, but with a qualification. The notch sensitivity factor depends on the cyclic ΔK_I level, as well as on the root radius, and it suddenly decreases at a ΔK_I of about $50 \text{ ksi}\cdot\text{in.}^{1/2}$. A conservative upper limit to the ΔK_I level to be used for initiating flaw growth by fatigue is $40 \text{ ksi}\cdot\text{in.}^{1/2}$. This value coincides with the value specified by current ASTM testing standards.
4. The/number of load cycles required to initiate flaw growth by fatigue, for a $2 \frac{1}{4}$ -in.-deep part-through flaw in a tensile specimen of A533-B steel, with a notch root radius of 0.015 in. and a cyclic ΔK_I of $40 \text{ ksi}\cdot\text{in.}^{1/2}$, is 2000 load cycles.
5. The/number of load cycles delay in fatigue flaw growth caused by reducing the ΔK_I level by ten percent, which is the maximum reduction in ΔK_I allowed by current ASTM testing procedures, is negligible.

6. The estimated number of load cycles required to propagate the crack the distance required by current ASTM testing standards is 15,000 load cycles. Therefore, 20,000 load cycles is a reasonable overall estimate of the number of load cycles required for fatigue crack sharpening.
7. A machined notch root radius of 0.015 in. is satisfactory for a 2 1/4-in.-deep notch. Not much would be gained by making the machined notch sharper.
8. The experimentally observed number of load cycles required to initiate fatigue crack growth is greater than the estimated number of load cycles, but not by enough to reduce the feasibility of notch sharpening by fatigue.

REFERENCES

1. T. H. Topper, R. M. Wetzel and J. Morrow, "Neuber's Rule Applied to Fatigue of Notched Specimens," Journal of Materials, 4(1): 200-209 (March 1969).
2. W. G. Clark, Jr. and L. J. Ceschini, "Fatigue Precracking of Spin-burst Toughness Specimens," Experimental Mechanics, 9(3): 123-128 (March 1969).
3. L. F. Kooistra, E. A. Lange and A. G. Pickett, "Full-Size Pressure Vessel Testing and Its Application to Design," Journal of Engineering for Power, ASME, October 1964, pp. 419-428.
4. B. F. Langer, "Application of Stress-Concentration Factors," pp. 1-12 in "Bettis Technical Review, Reactor Technology," WAPD-BT-18, Bettis Atomic Power Laboratory, April 1960.
5. R. E. Peterson, "Stress Concentration Design Factors," Wiley, 1953.
6. W. J. O'Donnell and C. M. Purdy, "The Fatigue Strength of Members Containing Cracks," Journal of Engineering for Industry, ASME, pp. 205-213 (May 1964).
7. H. Neuber, "Theory of Notch Stresses: Principles for Exact Calculation of Strength with Reference to Structural Form and Material," AEC-TR-4547, 1958, distributed by the Clearinghouse for Federal Scientific and Technical Information, Springfield, Virginia.
8. G. R. Irwin, J. M. Krafft, P. C. Paris and A. A. Wells, "Basic Aspects of Crack Growth and Fracture," Section 7 in, "Technology of Steel Pressure Vessels for Water-Cooled Nuclear Reactors," G. D. Whitman, G. C. Robinson, Jr. and A. W. Savolainen, editors, ORNL-NSIC-21, Oak Ridge National Laboratory, December 1967; (see also NRL Report 6598, U. S. Naval Research Laboratory, November 21, 1967).
9. P. Paris and F. Erdogan, "A Critical Analysis of Crack Propagation Laws," Journal of Basic Engineering, ASME, pp. 528-534 (December 1963).
10. G. R. Irwin, personal communication, March 9, 1970.
11. M. B. Bickell and C. Ruiz, "Pressure Vessel Design and Analysis," Macmillan, 1967.
12. A. S. Tetelman and A. J. McEvily, Jr., "Fracture of Structural Materials," Wiley, 1967.
13. R. G. Berggren, Oak Ridge National Laboratory, unpublished data.
14. W. G. Clark, Jr., Westinghouse Research Laboratories, personal communication, December 6, 1968.

15. S. S. Manson, "Thermal Stress and Low Cycle Fatigue," McGraw Hill, 1966.
16. D. F. Mowbray, W. R. Andrews and A. J. Brothers, "Fatigue-Crack Growth-Rate Studies of Low-Alloy Pressure-Vessel Steels," ASME Paper No. 68-PVP-23, September 1968.
17. "Proposed Method of Test for Plane-Strain Fracture Toughness of Metallic Materials," 1969 Book of ASTM Standards, Part 31, pp. 1099-1114.
18. J. R. Rice, "Mechanics of Crack Tip Deformation and Extension by Fatigue," pp. 247-311 in, "Fatigue Crack Propagation," ASTM Spec. Tech. Pub. 415, 1967.
19. S. Yukawa, "Evaluation of Periodic Proof Testing and Warm Prestressing Procedures for Nuclear Reactor Vessels," HSSTP-TR-1, General Electric Company, Schenectady, New York, July 1, 1969.
20. B. F. Langer, Memorandum on Fatigue Studies for the HSST Program, Westinghouse Electric Corporation, February 21, 1968.
21. L. F. Kooistra, Method for Fatigue Sharpening Machined Notch in Pressure Vessel, unpublished memorandum, Oak Ridge National Laboratory, Oak Ridge, Tennessee, April 28, 1970.
22. S. C. Grigory, Testing of 6-in.-Thick Flawed Tensile Specimens, Paper No. 26, Heavy Section Steel Technology Program, 4th Annual Information Meeting, Oak Ridge National Laboratory, Oak Ridge, Tennessee, March 31 - April 1, 1970.
23. G. C. Robinson, personal communication, Oak Ridge National Laboratory, June 1970.
24. P. N. Randall, Gross Strain Measure of Fracture Toughness of Steels, HSSTP-TR-3, TRW Systems Group, Redondo Beach, California, Nov. 1, 1969.
25. E. J. Beck, Plastic Strain Measurements Around a Semielliptical Surface Flaw, Martin Marietta Corporation, Denver, Colorado, May 1969.
26. F. W. Smith and M. J. Alavi, Stress-Intensity Factors for a Part-Circular Surface Flaw, pp. 793-800 in Part II, Proceedings of the First International Conference on Pressure Vessel Technology, Delft, the Netherlands, ASME, 1969.

27. S. C. Grigory, Southwest Research Institute, San Antonio, Texas, unpublished data, September 1970.

Figure 1

ORNL-DWG 70-12142

Figure 2

ORNL-DWG 70-12143

Figure 3

ORNL-DWG 70-12144

Figure 4

Figure 5

Figure 6

Figure 7

Figure 8

Figure 9

DIMENSIONS ARE IN INCHES

SECTION A-A

Figure 10

Figure 11

Figure 12

Figure 13