40 11/26
MASTER

DP-972

AEC RESEARCH AND DEVELOPMENT REPORT

**ISOLATING AMERICIUM AND CURIUM
FROM $\text{Al}(\text{NO}_3)_3$ - NaNO_3 - HNO_3
SOLUTIONS BY BATCH EXTRACTION
WITH TRIBUTYL PHOSPHATE**

H. E. Henry

RELEASED FOR ANNOUNCEMENT

IN NUCLEAR SCIENCE ABSTRACTS

Savannah River Laboratory

Aiken, South Carolina

LEGAL NOTICE

This report was prepared as an account of Government sponsored work. Neither the United States, nor the Commission, nor any person acting on behalf of the Commission:

A. Makes any warranty or representation, expressed or implied, with respect to the accuracy, completeness, or usefulness of the information contained in this report, or that the use of any information, apparatus, method, or process disclosed in this report may not infringe privately owned rights; or

B. Assumes any liabilities with respect to the use of, or for damages resulting from the use of any information, apparatus, method, or process disclosed in this report.

As used in the above, "person acting on behalf of the Commission" includes any employee or contractor of the Commission, or employee of such contractor, to the extent that such employee or contractor of the Commission, or employee of such contractor prepares, disseminates, or provides access to, any information pursuant to his employment or contract with the Commission, or his employment with such contractor.

Printed in USA. Price \$1.00

Available from the Clearinghouse for Federal Scientific
and Technical Information, National Bureau of Standards,
U. S. Department of Commerce, Springfield, Virginia

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency Thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

DISCLAIMER

Portions of this document may be illegible in electronic image products. Images are produced from the best available original document.

LEGAL NOTICE

This report was prepared as an account of Government sponsored work. Neither the United States, nor the Commission, nor any person acting on behalf of the Commission:

A. Makes any warranty or representation, expressed or implied, with respect to the accuracy, completeness, or usefulness of the information contained in this report, or that the use of any information, apparatus, method, or process disclosed in this report may not infringe privately owned rights; or

B. Assumes any liabilities with respect to the use of, or for damages resulting from the use of any information, apparatus, method, or process disclosed in this report.

As used in the above, "person acting on behalf of the Commission" includes any employee or contractor of the Commission, or employee of such contractor, to the extent that such employee or contractor of the Commission, or employee of such contractor prepares, disseminates, or provides access to, any information pursuant to his employment or contract with the Commission, or his employment with such contractor.

DP-972

Chemical Separations Processes
for Plutonium and Uranium
(TID-4500, 45th Ed.)

ISOLATING AMERICIUM AND CURIUM FROM $\text{Al}(\text{NO}_3)_3$ - NaNO_3 - HNO_3 SOLUTIONS BY BATCH EXTRACTION WITH TRIBUTYL PHOSPHATE

by

Hugh E. Henry

Approved by

L. H. Meyer, Research Manager
Separations Chemistry Division

August 1965

RELEASED FOR ANNOUNCEMENT
IN NUCLEAR SCIENCE ABSTRACTS

E. I. DU PONT DE NEMOURS & COMPANY
SAVANNAH RIVER LABORATORY
AIKEN, SOUTH CAROLINA

CONTRACT AT(07-2)-1 WITH THE
UNITED STATES ATOMIC ENERGY COMMISSION

ABSTRACT

Batch solvent extraction was used to isolate ^{243}Am and ^{244}Cm from the aqueous solution remaining after dissolution of an irradiated Pu-Al alloy in nitric acid and recovery of the Pu by anion exchange. The solution was adjusted to 6.5-6.8M inextractable nitrate and 0.10-0.35M HNO_3 before extracting the Am-Cm with an equal volume of 50 volume percent tri-n-butyl phosphate in a hydrocarbon diluent and then back-extracting into 0.2M HNO_3 . Recovery was greater than 95% with up to one-liter batches in laboratory tests and with 1500-gallon batches on a plant scale. Factors affecting the degree of extraction were measured in the laboratory.

CONTENTS

	<u>Page</u>
LIST OF TABLES AND FIGURES	iv
INTRODUCTION	1
SUMMARY	2
DISCUSSION	3
Preliminary Evaluation	3
Distribution Data	6
Laboratory Demonstrations with Simulated Feed	12
Laboratory Demonstrations with Irradiated Pu-Al Alloy Solutions	15
Plant Performance with Irradiated Pu-Al Alloy Solutions	17
BIBLIOGRAPHY	18

LIST OF TABLES AND FIGURES

Table		<u>Page</u>
I	Density and Viscosity of Typical Aqueous Feed Solutions and of 50 and 75 vol % TBP in "Adakane 12" .	5
II	Conditions and Results of Preliminary Test	6
III	Americium and Europium Recovery from Simulated Feed .	13
IV	Summary of Results Obtained with Am-Cm Solutions Containing Mixed Fission Products	14
V	Summary of Results Obtained in the Laboratory with Solutions of Irradiated Pu-Al Alloy	16
VI	Summary of Results Obtained by Plant with Solutions of Irradiated Pu-Al Alloy	17
VII	Typical Solvent Washing Results in Plant	18

Figure

1	Calculated Interface Levels in a Plant-Size Decanter for Stripping Step	4
2	Effect of Nitrate on Extraction of Americium and Europium	7
3	Effect of Acid on Extraction of Americium and Europium	8
4	Effect of Acid on Americium Losses	9
5	Effect of Temperature on Extraction of Americium and Europium	10
6	Distribution of Nitric Acid	11

ISOLATING AMERICIUM AND CURIUM FROM $\text{Al}(\text{NO}_3)_3\text{-NaNO}_3\text{-HNO}_3$ SOLUTIONS BY BATCH EXTRACTION WITH TRIBUTYL PHOSPHATE

INTRODUCTION

Plutonium-aluminum alloy has been irradiated in a Savannah River reactor to produce a mixture of ^{242}Pu , ^{243}Am , and ^{244}Cm that will be irradiated in the High Flux Isotopes Reactor (HFIR) at Oak Ridge to produce transcurium elements.⁽¹⁾ In a second program,⁽²⁾ Pu-Al is being irradiated to produce 3 kg of ^{244}Cm that will be used to demonstrate the usefulness of this isotope as a heat source for space applications.^(3,4,5)

The Pu-Am-Cm mixture produced for further irradiation was isolated in two separate chemical processing campaigns. In the first campaign, the irradiated alloy was dissolved by a two-step procedure involving initial dissolution of the aluminum matrix in NaOH-NaNO_3 solution, followed by acidification of the mixture with nitric acid and final dissolution of the remaining solids.^(6,7) Plutonium was isolated from the solution by anion exchange^(8,9), while Al, Am, Cm, and the fission products remained in the raffinate. Am, Cm, and the rare earths were then separated from the large quantity of aluminum nitrate and sodium nitrate by precipitation of double sodium actinide sulfates.⁽⁹⁾ Finally, the mixture of double sulfates was metathesized with sodium hydroxide and dissolved in a small volume of nitric acid for shipment to Oak Ridge, where the Am and Cm will be purified and fabricated into targets for the HFIR. Plutonium also has been separated from a similar dissolver solution of plutonium-aluminum alloy by solvent extraction with tributyl phosphate.⁽¹⁰⁾

All of the processing steps in the second campaign were identical with those in the first campaign except that the Am, Cm, and rare earths were isolated from the anion exchange raffinate by batch extraction with 50 vol % tributyl phosphate.

This report describes the development and performance of the batch extraction process. According to present plans, this process will be used to isolate the mixture of ^{243}Am , ^{244}Cm , and fission products from the raffinates that will be generated in processing the irradiated Pu-Al alloy associated with the production of the 3 kg of ^{244}Cm .

SUMMARY

Batch solvent extraction was used successfully to isolate a mixture of Am-Cm and rare earth fission products from irradiated Pu-Al alloy that had previously been dissolved in HNO_3 and processed by anion exchange to recover residual plutonium. The sequence of steps for the process are:

- (1) The $\text{Al}(\text{NO}_3)_3$ - HNO_3 solution containing the Am-Cm and fission products is adjusted to 6.5-6.8M inextractable nitrate and 0.10-0.35M HNO_3 .
- (2) The actinides and lanthanides are extracted from the adjusted solution with an equal volume of 50 vol % TBP in a hydrocarbon diluent; the $\text{Al}(\text{NO}_3)_3$ is not extracted and most of the non-rare earth fission products are only partially extracted. The aqueous waste may then be readjusted to 0.10-0.35M HNO_3 and extracted again to recover the small fraction (1-5%) of actinides remaining after the first extraction.
- (3) The Am-Cm and lanthanides are stripped from the organic phase with two half-volumes of 0.2M HNO_3 .
- (4) The used solvent is washed before reuse with NaOH or Na_2CO_3 solution to remove fission products and the dibutyl phosphate formed by radiolysis.
- (5) The aqueous solution of Am-Cm and lanthanides is washed with a hydrocarbon, such as n-dodecane, to ensure that excessive TBP does not enter the evaporator, and the solution is then concentrated by evaporation.

Am-Cm yields in excess of 95% were obtained in laboratory tests and on 1500-gallon batches in large plant equipment.

DISCUSSION

PRELIMINARY EVALUATION

The feasibility of extracting americium and curium from $\text{Al}(\text{NO}_3)_3$ - HNO_3 solutions into dilute TBP was demonstrated by previous studies:

- Distribution data for $\text{Am}(\text{NO}_3)_3$ extraction into 35 vol % TBP from 0-5M NaNO_3 - 0-5M HNO_3 solutions showed that americium is extracted as a TBP complex, and that HNO_3 depresses extraction by competing for TBP and by complexing americium in the aqueous phase as $\text{HAm}(\text{NO}_3)_4$.⁽¹¹⁾
- The americium distribution coefficient between 33 vol % TBP and aqueous solutions containing 5M total nitrate was 3 for NaNO_3 , 30 for $\text{Ca}(\text{NO}_3)_2$, and 100 for $\text{Al}(\text{NO}_3)_3$.⁽¹²⁾
- The distribution coefficient for curium between 100% TBP and 7.2M NaNO_3 -0.4M HNO_3 was 100.⁽¹³⁾

These previous studies indicated that 100% TBP would be satisfactory with high concentrations of inextractable nitrate, if the HNO_3 concentration were sufficiently low to prevent serious competition for the TBP. In an initial scouting experiment >90% of the Am was extracted by 100% TBP from a solution of 0.7M $\text{Al}(\text{NO}_3)_3$ -3.5M NaNO_3 -0.9M HNO_3 -0.002M $\text{Nd}(\text{NO}_3)_3$ - ^{241}Am tracer, with an organic-to-aqueous ratio of 0.2.

Although extraction coefficients are high with 100% TBP, 50% TBP was chosen because it could be more easily separated from the aqueous strip solution (0.2M HNO_3). Interface levels for the decanter to be used in the plant are illustrated in Figure 1. Undiluted TBP cannot be separated readily from the aqueous strip because the density difference is negligible. Solvents containing 50-75 vol % TBP are practical; however, for 75 vol % TBP 3-4M HNO_3 would be required to maintain the interface level near the middle of the decanter. An additional advantage of using 50% TBP is its lower viscosity, which aids settling of emulsions in the decanter. Density and viscosity data are summarized in Table I.

FIG. 1 CALCULATED INTERFACE LEVELS IN A PLANT - SIZE DECANter FOR STRIPPING STEP

TABLE I

Density and Viscosity of Typical Aqueous Feed Solutions
and of 50 and 75 vol % TBP in "Adakane 12"*

Solution	Temp, °C	Density, g/ml	Kinematic Viscosity, centistokes
0.6M Al ³⁺ -0.18M H ⁺ -	24	1.328	2.33
6.3M NO ₃ ⁻ -4.3M Na ⁺ -	50	1.315	1.74
0.05M Fe ³⁺ -0.1M SO ₄ ²⁻	70	1.299	1.31
0.6M Al ³⁺ -0.44M H ⁺ -	24	1.368	2.65
7.0M NO ₃ ⁻ -4.8M Na ⁺ -	50	1.349	1.81
0.05M Fe ³⁺ -0.1M SO ₄ ²⁻	70	1.336	1.45
50 vol % TBP in "Adakane 12"*	24	0.865	2.76
	50	0.846	2.09
	70	0.831	1.75
75 vol % TBP in "Adakane 12"*	24	0.921	3.40
	50	0.898	2.58
	70	0.883	1.95

*Product of Archer Daniels Midland Co.

A preliminary test showed that Am-Cm extraction with 49% TBP was feasible. In this test, anion exchange raffinate from irradiated Pu-Al alloy (previously dissolved by the two-step procedure) was adjusted to 0.3M HNO₃, contacted at an organic-to-aqueous ratio of 0.5, and then stripped three times with half volumes of 1M HNO₃. The conditions and results are shown in Table II.

TABLE II

Conditions and Results of Preliminary Test

Feed:

0.3M H⁺, 0.7M Al³⁺, 4.1M Na⁺, 0.02M Fe³⁺,
0.04M SO₄²⁻, 6.5M NO₃⁻, 2.5x10⁹ d/m/ml gross α,
9.5x10⁸ c/m/ml gross γ

Solvent:

49 vol % TBP in "Adakane 12"*

Organic-to-Aqueous Volume Ratio:

0.5 for extraction, 2 for stripping

Strip Solution: 1M HNO₃

Temperature: 25°C

<u>Strip No.</u>	<u>Cumulative Am-Cm Recovery, %</u>
1	73.7
2	83.2
3	84.1
% Am-Cm not extracted from feed	15.5
% Am-Cm retained in organic phase after 3 strips	0.4

*Product of Archer Daniels Midland Co.

DISTRIBUTION DATA

To define the conditions for recovering >95% of the Am-Cm, ²⁴¹Am (to indicate actinide extraction efficiency) and ¹⁵²⁻¹⁵⁴Eu (to indicate rare earth extraction efficiency) were extracted with 50 vol % TBP from simulated solutions in which the concentrations of Al(NO₃)₃, and total inextractable nitrate were varied independently and temperature was varied from 25 to 70°C. The results, shown in Figures 2-5, indicate recovery was satisfactory from aqueous solutions containing 6.5-7.5M total nitrate and 0.1-0.36M HNO₃ at an organic-to-aqueous volume ratio of 1. Higher concentrations of inextractable nitrate increase extraction, as shown in Figure 2, while higher HNO₃ concentrations decrease extraction, as shown in Figures 3 and 4. Smaller organic-to-aqueous volume ratios would decrease extraction because a greater fraction of the TBP would be complexed by HNO₃, resulting in back-salting of the Am-Cm. Extraction decreased at higher temperatures (Figure 5).

Nitric acid extraction at ~6.5M inextractable nitrate is shown in Figure 6. Extrapolation of these data indicates that with ~0.1M HNO₃ in the feed, the aqueous acid after extraction would be ≤0.01M which might be too low to prevent precipitation of some of the cations, especially iron. Proper adjustment of the feed acid is required to prevent undesirable precipitates.

FIG. 2 EFFECT OF NITRATE ON EXTRACTION OF AMERICIUM AND EUROPIUM

FIG. 3 EFFECT OF ACID ON EXTRACTION OF AMERICIUM AND EUROPIUM

FIG. 4 EFFECT OF ACID ON AMERICIUM LOSSES

FIG. 5 EFFECT OF TEMPERATURE ON EXTRACTION OF AMERICIUM AND EUROPIUM

FIG. 6 DISTRIBUTION OF NITRIC ACID

LABORATORY DEMONSTRATIONS WITH SIMULATED FEED

Aqueous feeds were simulated by adding either ^{241}Am and $^{152-154}\text{Eu}$ tracers or ^{243}Am , ^{244}Cm , and mixed fission products (from irradiated ^{235}U)* to $\text{Al}(\text{NO}_3)_3$ - NaNO_3 - HNO_3 solutions. The extraction procedures involved a single extraction with equal volumes of organic and aqueous phases followed by two consecutive strips with 0.2M HNO_3 using two volumes of organic solution per volume of aqueous strip solution. In one test, 0.2 vol % dibutyl phosphate was added to simulate severe radiolytic degradation of TBP.

In the tests with ^{241}Am and $^{152-154}\text{Eu}$ tracers, over-all yields of both americium and europium were >98% with 0.05M HNO_3 in the feed, but were ~93% with 0.5M HNO_3 . The addition of 0.2 vol % DBP had no effect in either the extraction or the stripping steps. A summary of these results is given in Table III.

In the tests with feeds containing ^{243}Am , ^{244}Cm , and mixed fission products, over-all curium yields were >95%. Decontamination factors were normally 2-3 for ruthenium and 10-30 for zirconium. Essentially no aluminum or fission products other than lanthanides, Zr, and Ru were extracted. Results with mixed fission products are summarized in Table IV.

Interfacial emulsions and solids (mostly Al, Na, and La) formed during extraction when the concentration of inextractable nitrate was 8.6M. The solution of mixed fission products used in this test contained solids and was not filtered prior to use. Apparently both the excess nitrate, which caused excessive HNO_3 extraction and an acid deficient aqueous phase after extraction, and the original solids in the mixed fission products contributed to the emulsions and solids. Emulsions and interfacial precipitates were considerably decreased when the feed was diluted to 7.1M inextractable nitrate. Curium recovery was 96-99%, decontamination factors were normal, and the phases were satisfactorily separated when centrifuged.

*Addition of fission products by blending in the wastes from processing irradiated uranium was required to simulate the level of fission products expected in the irradiated plutonium systems that will result from the early phases of a curium production program.

TABLE III

Americium and Europium Recovery from Simulated Feed

Aqueous Feed ^(a)		Organic Phase ^(b)		Strip Solution ^(c)				
HNO ₃ , M	Total NO ₃ ⁻ , M	% Am Extracted	% Eu Extracted	Strip No.	Cumulative Recovery, %		Retained by Solvent, %	
					Am	Eu	Am	Eu
0.5	6.4	93	96	1	88	90	5	6
				2	92.8	95.7	0.2	0.3
0.05	6.4	98	99	1	95	96.5	3	2.5
				2	98	98.7	0.03	0.3
0.05	6.4	98 ^(d)	99	1	95	96.5	3	2.5
				2	98	98.7	0.03	0.3

(a) Simulated Pu Recovery Wastes: 0.7M Al³⁺, 3.8-4.3M Na⁺, 0.002M Nd³⁺, ²⁴¹Am and ¹⁵²⁻¹⁵⁴Eu tracers.

(b) 50 vol % TBP in "Adakane 12"* for equal volume extractions.

(c) 0.2M HNO₃ for half volume strips.

(d) 0.2 vol % DBP added to solvent.

*Product of Archer Daniels Midland Co.

TABLE IV

Summary of Results Obtained with Am-Cm Solutions Containing Mixed Fission Products

	Fission Products from Process Wastes from <u>Irradiated Natural Uranium</u>		Fission Products from Process Wastes from <u>Irradiated ²³⁵U-Al Alloy</u>			
<u>Aqueous Composition of Feed Before Extraction</u>						
Test Solution, ml →	<u>10</u>	<u>10</u>	<u>10</u>	<u>10</u>	<u>1000</u>	<u>1300</u>
Al ³⁺ , M	2.16	2.15	2.03	2.15	2.39	1.95
Na ⁺ , M	-	-	-	-	1.1	0.9
NO ₃ ⁻ , M	6.9	6.6	6.3	6.6	8.6	7.1
H ⁺ , M	0.38	0.15	0.25	0.18	0.30	0.33
Cm, g/l	0.80	0.80	0	0	0.72	0.58
α, d/(min)(ml)	1.40x10 ¹¹	1.40x10 ¹¹	-	-	1.26x10 ¹¹	1.02x10 ¹¹
¹⁴⁴ Ce- ¹⁴⁴ Pr, d/(sec)(ml)	6.9x10 ⁷	8.0x10 ⁷	5.4x10 ⁷	8.4x10 ⁷	8.9x10 ⁷	6.6x10 ⁷
⁹⁵ Zr- ⁹⁵ Nb, d/(sec)(ml)	3.5x10 ⁷	2.6x10 ⁷	-	-	1.2x10 ⁸	1.0x10 ⁸
¹⁰³ Ru, ¹⁰⁶ Ru- ¹⁰⁶ Rh, d/(sec)(ml)	7.8x10 ⁷	6.5x10 ⁷	1.4x10 ⁸	1.8x10 ⁸	2.5x10 ⁸	1.5x10 ⁸

Extraction: Equal volumes of aqueous feed and 50 vol % TBP in "Adakane 12"
(Product of Archer Daniels Midland Co.).

Yield of aqueous feed, %

Cm extracted into solvent	96	97	-	-	99.6	97
Ce extracted into solvent	87	91	92	88	93	88
Cm in strip solutions	95.7	96.6	-	-	99.3	96.5
Ce in strip solutions	96.5	90.5	91.5	86.2	71	76.6

Decontamination factors

^{95}Zr - ^{95}Nb	7	8	-	-	10.5	29
^{103}Ru , ^{106}Ru - ^{106}Rh	38	20	2.5	1.7	3.0	2.5

Stripping: Half-volumes of 0.2M HNO_3 for each of 2 strips.

Activity in used solvent
after stripping steps

α , d/(min)(ml)	3.8×10^8	4.2×10^8	-	-	2.0×10^8	2.8×10^8
^{144}Ce - ^{144}Pr , d/(sec)(ml)	3.1×10^5	3.2×10^5	1.5×10^6	1.5×10^6	1.8×10^7	1.3×10^7
^{95}Zr - ^{95}Nb , d/(sec)(ml)	1.0×10^7	5.8×10^6	-	-	4.9×10^8	3.1×10^8
^{103}Ru , ^{106}Ru - ^{106}Rh , d/(sec)(ml)	2.2×10^6	3.8×10^6	2.0×10^7	2.5×10^7	9.2×10^7	1.5×10^7

Solvent Washing: Equal volumes of 0.5M Na_2CO_3 and stripped solvent.

Activity in solvent after
one carbonate wash

α , d/(min)(ml)	4.0×10^4	1.5×10^6	-	-	4.4×10^7	2.2×10^7
^{144}Ce - ^{144}Pr , d/(sec)(ml)	1.6×10^3	6.2×10^3	2.5×10^5	5.5×10^5	1.9×10^6	2.7×10^5
^{95}Zr - ^{95}Nb , d/(sec)(ml)	2.8×10^4	7.8×10^4	-	-	2.2×10^8	3.4×10^7
^{103}Ru , ^{106}Ru - ^{106}Rh , d/(sec)(ml)	9.7×10^4	6.2×10^4	1.5×10^6	8.5×10^6	3.9×10^7	4.0×10^6

LABORATORY DEMONSTRATIONS WITH IRRADIATED Pu-Al ALLOY SOLUTIONS

In tests with irradiated Pu-Al alloy solutions which had been previously processed by anion exchange to recover Pu, the over-all yields of curium were >96% with one extraction and >99% with two extractions (the HNO_3 was adjusted to the approximate acid concentration of the initial feed before the second extraction). Results are summarized in Table V.

There were no problems with emulsions or interfacial precipitates, but a small amount of white precipitate formed slowly from feed which had been adjusted to 0.1M HNO_3 in the plant; the amount of precipitate increased overnight to 2 vol %, and settled to the bottom of the aqueous phase after each extraction. The precipitate contained insignificant curium and was mostly Al and Fe; it dissolved in 0.6M HNO_3 . Precipitation was probably caused by the low HNO_3 concentration ($\leq 0.01\text{M}$) after extraction.

Precipitation during extraction was prevented by increasing the HNO_3 in the feed to 0.6M. The HNO_3 distribution data in Figure 6 indicate that $\geq 0.1\text{M}$ HNO_3 would remain in the aqueous after extraction if HNO_3 in the feed were 0.6M. Because the precipitate did not form at 0.1M before extraction, no precipitate should form after extraction. The higher initial acid decreases Am-Cm extraction (Figure 4), but the over-all recovery would not be significantly lowered with two or three sequential extractions.

Decontamination factors for Zr-Nb and Ru were essentially the same as those obtained when using simulated feed solutions containing mixed fission products.

Solvent washing with a solution of 0.8 wt % NaOH-2.5 wt % Na_2CO_3 , which is used in the plant, was slightly more effective in decontaminating the solvent than was 0.5M Na_2CO_3 .

TABLE V

Summary of Results Obtained in the Laboratory with Solutions of Irradiated Pu-Al-Alloy

	Feed Adjusted in Laboratory		Feed Adjusted in Plant (Two Extractions)	
	(One Extraction Only)	First Extraction	Second Extraction	Total
Aqueous Composition of Feed Before Extraction				
Test Solution, ml →	10	180	163	
Al ³⁺ , M	0.56	0.67	0.64	
Na ⁺ , M	4.8	4.7	4.5	
NO ₃ ⁻ , M	6.8	6.8	6.7	
H ⁺ , M	0.32	0.10	0.13	
α, d/(min)(ml)	1.97x10 ⁹	2.52x10 ⁹	7.00x10 ⁷	
⁹⁵ Zr- ⁹⁵ Nb, d/(sec)(ml)	1.37x10 ⁶	1.68x10 ⁷	1.36x10 ⁷	
¹⁰³ Ru, ¹⁰⁶ Ru- ¹⁰⁶ Rh, d/(sec)(ml)	2.10x10 ⁷	4.00x10 ⁷	1.46x10 ⁷	
¹⁴⁴ Ce- ¹⁴⁴ Pr, d/(sec)(ml)	2.85x10 ⁶	3.78x10 ⁶	4.70x10 ⁵	
¹³⁴ , ¹³⁷ Cs, d/(sec)(ml)	2.00x10 ⁸	2.10x10 ⁸	2.00x10 ⁸	
Extraction: Equal volumes of aqueous feed and 50 vol % TBP in "Adakane 12" (Product of Archer Daniels Midland Co.).				
Yield of aqueous feed, %				
Cm extracted into solvent	96.7	97.2	2.7	99.9
Ce extracted into solvent	86.4	87.0	3.9	90.9
Cm in strip solutions	96.5	96.8	2.5	99.3
Ce in strip solutions	86.0	86.4	3.4	89.8
Decontamination factors				
⁹⁵ Zr- ⁹⁵ Nb	18			29.1
¹⁰³ Ru, ¹⁰⁶ Ru- ¹⁰⁶ Rh	6			4.3
¹³⁴ , ¹³⁷ Cs	>4.2x10 ⁴			>4.2x10 ⁴
Stripping: Half-volumes of 0.2M HNO ₃ for each of 2 strips.				
Activity in used solvent after stripping steps				
α, d/(min)(ml)	1.5x10 ⁶	9.1x10 ⁶	4.1x10 ⁵	
¹⁴⁴ Ce- ¹⁴⁴ Pr, d/(sec)(ml)	5.0x10 ⁴	1.0x10 ⁴	5.0x10 ³	
⁹⁵ Zr- ⁹⁵ Nb, d/(sec)(ml)	5.0x10 ⁵	1.0x10 ⁵	8.3x10 ⁴	
¹⁰³ Ru, ¹⁰⁶ Ru- ¹⁰⁶ Rh, d/(sec)(ml)	2.4x10 ⁶	1.7x10 ⁷	2.1x10 ⁶	
Solvent Washing: Equal volumes of stripped solvent and either 0.5M Na ₂ CO ₃ or 0.8 wt % NaOH-2.5 wt % Na ₂ CO ₃ .				
Activity in solvent after one wash with →	0.5M Na ₂ CO ₃	0.8 wt % NaOH- 2.5 wt % Na ₂ CO ₃	0.8 wt % NaOH- 2.5 wt % Na ₂ CO ₃	
α, d/(min)(ml)	1.3x10 ⁵	5.0x10 ⁴	6.1x10 ³	
¹⁴⁴ Ce- ¹⁴⁴ Pr, d/(sec)(ml)	5.0x10 ²	6.7x10 ²	<50	
⁹⁵ Zr- ⁹⁵ Nb, d/(sec)(ml)	2.4x10 ⁴	2.2x10 ³	3.5x10 ²	
¹⁰³ Ru, ¹⁰⁶ Ru- ¹⁰⁶ Rh, d/(sec)(ml)	1.6x10 ⁴	9.7x10 ³	1.2x10 ³	

PLANT PERFORMANCE WITH IRRADIATED Pu-AI ALLOY SOLUTIONS

The laboratory procedures were successfully used on a 1500-gallon batch in Savannah River Plant equipment to recover ~500 grams of Am-Cm from irradiated Pu-AI alloy solutions which had been previously processed by anion exchange to recover Pu isotopes. Yields were normally $\geq 98\%$; about 96% yield was obtained in one test in which the aqueous fraction became acid deficient after the first extraction because of low HNO_3 in the feed. A generally lower extraction efficiency in the large equipment - attributed to recycling feed, raffinate, and product through the same tanks - was compensated by a third extraction to recover $>98\%$ of the Am-Cm. Normally, 91-95% was extracted in the first contact with solvent. A summary of results of the plant performance is given in Table VI.

During the plant operation the solvent was exposed to radiation for 12 to 30 hours. This exposure did not affect decontamination or Am-Cm yields. Typical plant solvent washing data for solvent used in the initial extraction are shown in Table VII; the data indicate that solvent washing was adequate and that degradation of the solvent was not too severe.

TABLE VI

Summary of Results Obtained by Plant with Solutions of Irradiated Pu-AI Alloy

Extraction: Equal volumes of aqueous feed and 50 vol % TBP
in "Ultrasene" (Product of Atlantic Refining Co.).

Stripping: Half-volumes of 0.25M HNO_3 for each of 2 strips.

Feed Batch	Curium Extracted Into Solvent, %				Cm Loss to Raffinate, %	Cm Loss to Solvent Washer, %	Cm in Strip Solution, %
	First Extraction	Second Extraction	Third Extraction	Total			
1	91.7	4.7	2.5	98.9	1.1	0.5	98.4
2	91.6	5.9	1.5	99.0	1.0	0.8	98.2
3	95.2	2.5	1.6	99.3	0.7	1.3	98.0
4*	85.9	4.3	6.1	96.3	3.7	0.3	96.0

*Aqueous phase was acid deficient after the first and second extractions and was readjusted to 0.2M HNO_3 before the third extraction. The acid-deficient solutions contained solids which did not dissolve after adjusting to 0.2M HNO_3 for the third extraction period.

TABLE VII

Typical Solvent Washing Results in Plant

Solvent: 50 vol % TBP in "Ultrasene"
(Product of Atlantic Refining Co.)

Solvent Washing: Equal volumes of stripped solvent
and 1 wt % NaOH-2.5% Na₂CO₃

Exposure of Solvent 12 to 30 hours at level of
to Cm α Activity: ~2.5x10⁹ d/(min)(ml)

<u>Activity in Solvent</u>	<u>Before Washing</u>	<u>After Washing</u>
α, d/(min)(ml)	1.5x10 ⁶	3.0x10 ⁴
	2.0x10 ⁷	1.5x10 ⁵
⁹⁵ Zr- ⁹⁵ Nb, d/(sec)(ml)	-	7.5x10 ⁴
¹⁰³ Ru, ¹⁰⁶ Ru- ¹⁰⁶ Rh, d/(sec)(ml)	-	4.5x10 ⁴

(a) 2.5% counting efficiency.

BIBLIOGRAPHY

1. "Transplutonium Element Production Program." Annual Report to Congress of the Atomic Energy Commission, 265. United States Atomic Energy Commission (1962).
2. "Savannah River Plant to Produce Curium-244." Isotopes and Radiation Technology 1, 206 (Winter 1963-1964).
3. D. H. Stewart, et al. Systems for Nuclear Auxiliary Power, An Evaluation, January 1964. USAEC Report TID-20079, USAEC Division of Reactor Development.
4. Chemical and Engineering News 42, No. 8, 39 (February 24, 1964).
5. "NASA Looking at Wide Mix of Nuclear Space Missions." Nucleonics 22, No. 6, p. 24 (1964).
6. W. C. Perkins. Dissolution of Pu-Al Alloy. USAEC Report DP-702, E. I. du Pont de Nemours and Co., Savannah River Laboratory, Aiken, S. C. (1962).
7. W. C. Perkins. Dissolving Highly Irradiated Pu-Al Alloy. USAEC Report DP-874, E. I. du Pont de Nemours and Co., Savannah River Laboratory, Aiken, S. C. (1964).

8. F. L. Culler, et al. Chemical Technology Division Annual Progress Report for Period Ending June 30, 1962. USAEC Report ORNL-3314, Union Carbide Corp., Oak Ridge National Laboratory, Oak Ridge, Tenn. (1962).
9. G. A. Burney and E. K. Dukes. Recovery of Americium and Curium from Irradiated Plutonium. USAEC Report DP- , E. I. du Pont de Nemours and Co., Savannah River Laboratory, Aiken, S. C. (to be published).
10. C. S. Schlea, et al. Recovery of Plutonium from Irradiated Plutonium-Aluminum Alloy. USAEC Report DP-739, E. I. du Pont de Nemours and Co., Savannah River Laboratory, Aiken, S. C. (1962).
11. K. A. Walsh. Extraction of Americium Nitrate with Tributyl Phosphate. USAEC Report LA-1861, Los Alamos Scientific Laboratory of the University of California, Los Alamos, N. M. (1955).
12. K. A. Walsh. Extraction of Americium Nitrate with Tributyl Phosphate, Paper No. 270, Nuclear Engineering and Science Congress, Cleveland, Ohio (1955).
13. J. J. Katz and G. T. Seaborg. The Chemistry of the Actinide Elements. John Wiley and Sons, Inc., New York, N. Y., p. 378 (1957).