THIS DOCUMENT CONFIRMED AS
UNCLASSIFIED
DIVISION OF CLASSIFICATION
BY JH/Calvin/EJT/amb
DATE 8/3/71

COO 841-21

Self-Diffusion in Liquid Indium*

M. Hsieh and R. A. Swalin
Department of Chemical Engineering and Materials Science
University of Minnesota, Minneapolis, Minnesota 55455

OK
8/3/71

Self-diffusion in liquid indium has been studied by Careri et al⁽¹⁾ and by Lodding⁽²⁾. There is some disagreement in the results and in addition Careri et al reported evidence for a wall effect. Diffusion coefficients calculated for samples held in capillaries of 0.83mm. I. D. were considerably lower than those calculated for samples held in 1.60 mm capillaries. These data are shown in Fig. 1. In the course of studies underway in our laboratory, it became necessary to know accurately the self-diffusivity in liquid indium. Consequently an investigation over a limited temperature range was undertaken by use of techniques different from those employed in ref. 1 and 2. The method used was analogous to the standard "thin layer" slicing method in the solid state. Following Larsson and Lodding's technique⁽³⁾ of preparing samples, a small amount of radioactive indium -114m was placed in the bottom of a 7cm precision bore long capillary tube. This tube was made of fused quartz and had an I. D. of one mm. The rest of the capillary was filled with inactive indium metal under vacuum.

A sample thus prepared was held at constant temperature in a silicone oil bath which was stirred continuously. By this technique the temperature variation

(1) G. Careri, A. Paoletti, and M. Vicentini, *Nuovo Cim.*, 10, 1088 (1958).

(2) A. Lodding, *Z. Naturforschung* 11a, 200 (1956).

(3) S. Larsson and A. Lodding, Private Communication.

* This research was supported by the U. S. Atomic Energy Commission.

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency Thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

DISCLAIMER

Portions of this document may be illegible in electronic image products. Images are produced from the best available original document.

was kept to less than one degree Celsius.

After diffusion annealing, the capillaries were cut into small sections which were about 5mm in length. Each section was carefully weighed and the activity was determined by standard radioactive tracer counting methods.

The small amount of radioactive tracer used as thin "film" weighed about 0.5 mg and was equivalent to a one mm long radioactive liquid cylinder at end of the 7cm long column. For comparison, this would correspond to a surface layer of about one μ m in thickness on a solid cylinder if a diffusion penetration of about one mm. were obtained. From the "thin film" solution of Fick's second law of diffusion⁽⁴⁾ the activity I along the capillary varies according to the following equation.

$$I = \text{constant} \cdot \frac{1}{\sqrt{Dt}} \cdot \exp \left(- \frac{x^2}{4Dt} \right) \quad (1)$$

where x is the distance along the cylinder axis from the closed end and t is the diffusion annealing time.

The diffusion coefficient D was calculated by measurement of the slope plot $\ln I$ versus x^2 . The diffusion coefficients obtained in this investigation are shown in Fig. 1.

It is observed that the data lie closely along the line determined by Lodding and show no evidence of the wall effect reported by Careri et al. Thus the results of this investigation which were obtained by a technique different from those employed previously for indium tend to support Lodding's diffusivity data and not those of Careri et al.

(4) P. G. Shewmon, Diffusion in Solids (McGraw-Hill Book Co., 1963).

FIGURE CAPTIONS

- (1) Self-diffusion in liquid indium as a function of temperature
-----1.60 mm. I. D. capillaries, ref. 1; -----0.83 mm. I. D.
capillaries, ref. 1; _____ ref. 2; • present data.

This report was prepared as an account of work sponsored by the United States Government. Neither the United States nor the United States Atomic Energy Commission, nor any of their employees, nor any of their contractors, subcontractors, or their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness or usefulness of any information, apparatus, product or process disclosed, or represents that its use would not infringe privately owned rights.

Fig. 1, Diffusion of Indium at constant pressure

Self-Diffusion in Liquid Indium*

M. Hsieh and R. A. Swalin
Department of Chemical Engineering and Materials Science
University of Minnesota, Minneapolis, Minnesota 55455

Self-diffusion in liquid indium has been studied by Careri et al⁽¹⁾ and by Lodding⁽²⁾. There is some disagreement in the results and in addition Careri et al reported evidence for a wall effect. Diffusion coefficients calculated for samples held in capillaries of 0.83mm. I. D. were considerably lower than those calculated for samples held in 1.60 mm capillaries. These data are shown in Fig. 1. In the course of studies underway in our laboratory, it became necessary to know accurately the self-diffusivity in liquid indium. Consequently an investigation over a limited temperature range was undertaken by use of techniques different from those employed in ref. 1 and 2. The method used was analogous to the standard "thin layer" slicing method in the solid state. Following Larsson and Lodding's technique⁽³⁾ of preparing samples, a small amount of radioactive indium -114m was placed in the bottom of a 7cm precision bore long capillary tube. This tube was made of fused quartz and had an I. D. of one mm. The rest of the capillary was filled with inactive indium metal under vacuum.

A sample thus prepared was held at constant temperature in a silicone oil bath which was stirred continuously. By this technique the temperature variation

- (1) G. Careri, A. Paoletti, and M. Vicentini, *Nuovo Cim.*, 10, 1088 (1958).
- (2) A. Lodding, *Z. Naturforschung* 11a, 200 (1956).
- (3) S. Larsson and A. Lodding, Private Communication.

* This research was supported by the U. S. Atomic Energy Commission.

was kept to less than one degree Celsius.

After diffusion annealing, the capillaries were cut into small sections which were about 5mm in length. Each section was carefully weighed and the activity was determined by standard radioactive tracer counting methods.

The small amount of radioactive tracer used as thin "film" weighed about 0.5 mg and was equivalent to a one mm long radioactive liquid cylinder at end of the 7cm long column. For comparison, this would correspond to a surface layer of about one μ m in thickness on a solid cylinder if a diffusion penetration of about one mm. were obtained. From the "thin film" solution of Fick's second law of diffusion⁽⁴⁾ the activity I along the capillary varies according to the following equation.

$$I = \text{constant} \cdot \frac{1}{\sqrt{Dt}} \cdot \exp \left(- \frac{x^2}{4Dt} \right) \quad (1)$$

where x is the distance along the cylinder axis from the closed end and t is the diffusion annealing time.

The diffusion coefficient D was calculated by measurement of the slope plot $\ln I$ versus x^2 . The diffusion coefficients obtained in this investigation are shown in Fig. 1.

It is observed that the data lie closely along the line determined by Lodding and show no evidence of the wall effect reported by Careri et al. Thus the results of this investigation which were obtained by a technique different from those employed previously for indium tend to support Lodding's diffusivity data and not those of Careri et al.

(4) P. G. Shewmon, Diffusion in Solids (McGraw-Hill Book Co., 1963).

FIGURE CAPTIONS

- (1) Self-diffusion in liquid indium as a function of temperature
-----1.60 mm. I. D. capillaries, ref. 1; -----0.83 mm. I. D.
capillaries, ref. 1; _____ ref. 2; • present data.

This report was prepared as an account of work sponsored by the United States Government. Neither the United States nor the United States Atomic Energy Commission, nor any of their employees, nor any of their contractors, subcontractors, or their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness or usefulness of any information, apparatus, product or process disclosed, or represents that its use would not infringe privately owned rights.

Fig. 1, Diffusion of Indium at constant pressure