5-38-68
137 Copies

~~CONFIDENTIAL~~

DECLASSIFIED
UNCLASSIFIED

MASTER

THE DESIGN
AND FABRICATION
OF

SPHERICAL FUEL CAPSULES

FOR
RADIOISOTOPE
GENERATORS (U)

HIT-260

JUNE 30, 1967

Hittman Associates, Inc.

Baltimore, Maryland

SPECIAL REREVIEW	Reviewer	Class.	Date
FINAL	GRP	U	03/02/82
DETERMINATION	KAW	U	03/08/82
Class: U			

~~CLASSIFICATION CANCELLED~~
~~OR CHANGED TO~~ UNCLASSIFIED
BY AUTHORITY OF D.O.C.
BY L. Topper DATE 11/2/71

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

DISTRIBUTION OF THIS DOCUMENT IS LIMITED
To Government Agencies and Their Contractors & CAC

68 9015
68 9487

~~RESTRICTED DATA~~
This document contains restricted data as defined in the Atomic Energy Act of 1954. Its transmittal or the disclosure of its contents in any manner to an unauthorized person is prohibited.

GROUP 1
Excluded from automatic
downgrading and
declassification

~~CONFIDENTIAL~~

DECLASSIFIED UNCLASSIFIED

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency Thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

DISCLAIMER

Portions of this document may be illegible in electronic image products. Images are produced from the best available original document.

~~CONFIDENTIAL~~

UNCLASSIFIED

(48)

THE DESIGN
AND FABRICATION
OF
SPHERICAL FUEL CAPSULES
FOR RADIOISOTOPE GENERATORS
FINAL REPORT
(U)

LEGAL NOTICE

This report was prepared as an account of Government sponsored work. Neither the United States nor the Commission nor any person acting on behalf of the Commission
A. Makes any warranty or representation expressed or implied with respect to the accuracy completeness or usefulness of the information contained in this report or that the use of any information apparatus method or process disclosed in this report may not infringe privately owned rights or
B. Assumes any liabilities with respect to the use of or for damages resulting from the use of any information apparatus method or process disclosed in this report
As used in the above person acting on behalf of the Commission includes any employee or contractor of the Commission or employee of such contractor to the extent that such employee or contractor of the Commission or employee of such contractor prepares disseminates or provides access to any information pursuant to his employment or contract with the Commission or his employment with such contractor

HIT-260

June 30, 1967

Prepared Under
AEC Contract No. AT(29-2)-2072

~~RESTRICTED DATA~~

This document contains restricted data as defined in the Atomic Energy Act of 1954. Its transmittal or the disclosure of its contents in any manner to an unauthorized person is prohibited.

GROUP 1
Excluded from automatic
downgrading and
declassification

HITTMAN ASSOCIATES, INC.
BALTIMORE, MARYLAND

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

~~CONFIDENTIAL~~

UNCLASSIFIED

DISTRIBUTION OF THIS DOCUMENT IS LIMITED
To Government Agencies and Their Contractors & CAP

~~CONFIDENTIAL~~

UNCLASSIFIED

LEGAL NOTICE

This report was prepared as an account of Government sponsored work. Neither the United States, nor the United States Atomic Energy Commission (Commission), nor any person acting on behalf of the Commission:

A. Makes any warranty or representation, expressed or implied with respect to the accuracy, completeness, or usefulness of the information contained in this report, or that the use of any information, apparatus, method, or process disclosed in this report may not infringe privately owned rights; or

B. Assumes any liabilities with respect to the use of, or for damages resulting from the use of any information, apparatus, method or process disclosed in this report.

As used in the above, "person acting on behalf of the Commission" includes any employee or contractor of the Commission, or employee of such contractor, to the extent that such employee or contractor of the Commission, or employee of such contractor prepares, disseminates, or provides access to, any information pursuant to this employment or contract with the Commission, or his employment with such contractor.

~~CONFIDENTIAL~~

UNCLASSIFIED

~~CONFIDENTIAL~~

DECLASSIFIED

TABLE OF CONTENTS

	<u>Page</u>
LEGAL NOTICE	ii
TABLE OF CONTENTS	iii
LIST OF TABLES	v
LIST OF FIGURES	vi
ABSTRACT	xii
I. SUMMARY	1
II. INTRODUCTION	3
A. Advantages of Spherical Capsules	3
B. Program Objectives	6
C. Design Criteria	7
III. SPHERICAL CAPSULE ANALYSIS	9
A. Initial Sizing	9
B. Aerothermodynamic Analysis	22
C. Capsule Creep Analysis	49
D. Capsule Burst Pressures	54
E. Impact Analysis	54
F. Performance Test Capsule Design	82
IV. CAPSULE DEVELOPMENT AND FABRICATION	90
A. Materials Procurement	90
B. Capsule Components Procurement	90
C. Tooling Design and Fabrication	96

~~CONFIDENTIAL~~

DECLASSIFIED

0315547030

~~CONFIDENTIAL~~TABLE OF CONTENTS (CONTINUED)

	<u>Page</u>
D. Welding and Assembly Development	99
E. Fabrication of Performance Test Capsules	122
V. PERFORMANCE TESTING AND EVALUATION	128
A. Details of the Test Program	128
B. Test Results	132
C. Performance Test Evaluation	152
REFERENCES	154
APPENDIX A - COMPUTER LOGIC DIAGRAMS	155
APPENDIX B - OXIDATION OF Ta-10%W ALLOY UNDER REENTRY CONDITIONS	159
APPENDIX B REFERENCES	163

~~CONFIDENTIAL~~

0317064030

~~CONFIDENTIAL~~

RESTRICTED

LIST OF TABLES

<u>Table No.</u>	<u>Title</u>	<u>Page</u>
III-1	Spherical Capsule Design Specifications	22
III-2	Aerodynamic and Physical Data Used In Analysis of Two Inch Spheres	26
III-3	Spherical Fuel Capsule Equilibrium Temperatures Under Convective Cooling	46
III-4	Capsule Weights and Test Velocities	68
III-5	Kinetic Energy Comparison Prior to Impact	70
III-6	Mechanical Design Criterion	83
III-7	Liner Volume	89
IV-1	Haynes-25 (L-605) Stock	91
IV-2	Tantalum-10 Tungsten Stock	92
IV-3	Molybdenum and Tungsten Powders Certified Property Data	93
IV-4	Tensile Test Data for Flat Plate Haynes-25 Stock	107
IV-5	Data On Delivered Impact Test Capsules	125
V-1	Summary of Performance Test Program	129
V-2	Results of Burst Pressure Tests	134
V-3	Results of Impact Tests	140

~~CONFIDENTIAL~~

RESTRICTED

0315587377

~~CONFIDENTIAL~~LIST OF FIGURES

<u>Figure No.</u>	<u>Title</u>	<u>Page</u>
II-1	Comparison of Impact Characteristics for Spherical Cylindrical Capsules	5
II-2	Specific Power Comparison of Cylindrical and Spherical Capsules Based on Creep Alone	5
II-3	Comparison of Three Inch Spherical and Cylindrical Capsules Based on Impact, Creep, and Burnup	5
III-1	Spherical Capsule Analytical Model	10
III-2	Sphere Drag Coefficient, C_D	15
III-3	Ta-10W Pressure Vessel Thickness Required to Withstand He Pressure vs. Capsule Diameter	17
III-4	Outer Shell Thickness vs. Diameter for Haynes-25/Ta-10W Capsule	17
III-5	Terminal Velocity vs. Diameter for Haynes-25/Ta-10W Capsule	18
III-6	EOL Thermal Power vs. Diameter for Haynes-25/Haynes-25	19
III-7	Weight vs. Diameter for Haynes-25/Haynes-25 Capsule	19
III-8	Haynes-25 Pressure Vessel Thickness Required to Withstand He Pressure vs. Capsule Diameter	20
III-9	Outer Clad Thickness vs. Diameter for Haynes-25/Haynes-25 Capsule	20
III-10	Terminal Velocity vs. Diameter for Haynes-25/Haynes-25 Capsule	21
III-11	Stagnation Point Heating Rate for One Inch Sphere	24

~~CONFIDENTIAL~~

0315587377

~~CONFIDENTIAL~~

LIST OF FIGURES (CONTINUED)

<u>Figure No.</u>	<u>Title</u>	<u>Page</u>
III-12	Stagnation Point Heating Rate for Three Inch Sphere	24
III-13	Integrated Stagnation Point Heat Flux vs. Capsule Diameter	24
III-14	Capsule Diameter Trajectory and Heating Rate for Two Inch Sphere for Release at 283, 000 Ft.	27
III-15	Trajectory and Heating Rate for Two Inch Sphere Following Abort	27
III-16	Terminal Velocity of Spherical Capsules	29
III-17	Nominal Ascent Trajectory	32
III-18	Spherical Capsule Two-Dimensional Model	33
III-19	Thermal Model Nodal Arrangement	34
III-20	Spherical Capsule Thermal-Electrical Analog	35
III-21	Temperature Transient for 2.2 Inch Sphere with Stagnation Heating After Orbital Decay	38
III-22	Temperature Transients for 2.2 Inch Sphere with Uniform Heating After Orbital Decay	38
III-23	Temperature Transients for 2.0 Inch Haynes-25/Ta-10W Configuration	40
III-24	Temperature Distribution for Haynes-25/Ta-10W Sphere	40
III-25	Temperature Transients for 2.0 Inch Haynes-25/Haynes-25 Capsule	40
III-26	Burnup Zones for Two Inch Capsule	42
III-27	Terminal Temperature vs. Capsule Radius	44

~~CONFIDENTIAL~~

~~CONFIDENTIAL~~

LIST OF FIGURES (CONTINUED)

<u>Figure No.</u>	<u>Title</u>	<u>Page</u>
III-28	Terminal Temperature Results for Two Inch Sphere	45
III-29	Impact Test Temperature Transient Analysis	48
III-30	Larson-Miller Data for Haynes-25	51
III-31	Larson-Miller Data for Ta-10W	51
III-32	Percent Creep vs. Time for Haynes-25/ Ta-10W Capsule	52
III-33	Percent Creep vs. Time for Haynes-25/ Haynes-25 Capsule (Single Shell)	53
III-34	Percent Creep vs. Time for Haynes-25/ Haynes-25 Capsule (Double Shell)	53
III-35	Percent Creep vs. Time for Haynes-25/ Haynes-25 Various Void Fractions	55
III-36	Percent Creep vs. Time for Haynes-25/ Ta-10W at Various Void Fractions	55
III-37	Pressure Required to Attain Yield and Ultimate Stresses vs. Temperature for Haynes-25/Haynes-25 Capsule	56
III-38	Pressure Required to Attain Yield and Ultimate Stresses vs. Temperature for Haynes-25/ Ta-10W Capsule	57
III-39	Schematic of Deformation of a Cylindrical Capsule Impacting	59
III-40	Haynes-25/Haynes-25 Capsules; Profiles Before & After Impact, Scale 1:1	60
III-41	Impact Deformation of Thick Walled Hemispherical Cylindrical Sample, Scale 4:1	63
III-42	Geometry of Impacting Spherical Capsule	66
III-43	Stress-Strain Relationships for Haynes-25 at 600°F	69

~~CONFIDENTIAL~~

~~CONFIDENTIAL~~

LIST OF FIGURES (CONTINUED)

<u>Figure No.</u>	<u>Title</u>	<u>Page</u>
III-44	Assumed Impacted Shape	72
III-45	Tensile Model	73
III-46	Compression Model	75
III-47	Experiment and Analysis Comparison	81
III-48	General Configuration of the Spherical Capsule	85
III-49	Spherical Capsule Component Details	87
III-50	Spherical Capsule Tolerance Study	88
IV-1	Fabricated Spherical Capsule Components	95
IV-2	Flat Plate Welding Jig	97
IV-3	Spherical Welding Jig	98
IV-4	Flat Plate Weld Specimens	101
IV-5	Cross Sectional Configurations of Flat Plate Weld Joints	103
IV-6	Photomicrographs Haynes-25 Plate Welds	106
IV-7	Photomicrographs Tantalum - 10 w/o Tungsten	106
IV-8	Flat Plate Ring Weld Specimens	109
IV-9	Capsule Fabrication Sequence	111
IV-10	Welding Chill Configurations (Cross Sectional Views)	112
IV-11	Fill Hole Configuration (For Fuel and Helium)	115
IV-12	Development Phase Spherical Capsule Haynes-25/Haynes-25 System	121

~~CONFIDENTIAL~~

03115 047133
~~CONFIDENTIAL~~

LIST OF FIGURES (CONTINUED)

<u>Figure No.</u>	<u>Title</u>	<u>Page</u>
IV-13	Photomicrographs of Qualification Capsule Weld Joints Haynes-25/ Haynes-25 System	124
IV-14	Creep Test Specimen Drawing	126
V-1	Creep-Burst Test Specimen	133
V-2	Burst Test Specimen	135
V-3	Photomicrographs Burst Test Specimens	137
V-4	Development Phase Capsules Haynes-25/ Haynes-25 System	141
V-5	Surface Views of Development Phase Impact Specimens Haynes-25/Haynes-25 System (Pole to Pole Section)	142
V-6	Internal Views of Development Phase Impact Specimens Haynes-25/Haynes-25 System (Pole to Pole Section)	143
V-7	Photomicrographs of Development Phase Impact Specimens Haynes-25/Haynes-25 System (T-2 Series)	144
V-8	Surface Views of Production Phase Impact Specimens Haynes-25/Haynes-25 System (Pole to Pole Section)	145
V-9	Internal Views of Production Phase Impact Specimens Haynes-25/Haynes-25 System (Pole to Pole Section)	146
V-10	Photomicrographs of Production Phase Impact Specimens Haynes-25/Haynes-25 System (PR-6 Series)	148
V-11	Surface Views of Production Phase Impact Specimens Haynes-25/Ta-10W System (Pole to Pole Section)	149

-X-
~~CONFIDENTIAL~~
03115 047133

~~CONFIDENTIAL~~

~~DECLASSIFIED~~

LIST OF FIGURES (CONTINUED)

<u>Figure No.</u>	<u>Title</u>	<u>Page</u>
V-12	Internal Views of Production Phase Impact Specimens Haynes-25/Ta-10W System (Pole to Pole Section)	150
V-13	Photomicrograph Composite of Fuel Plug Area on Inner Liner of Specimens PR-106 & PR-109 Haynes-25/Ta-10W System	151
V-14	Photomicrographs of Production Phase Impact Specimens Haynes-25/Ta-10W System (PR-109 Series)	153
A-1	Flow Logic Diagram for CAPSPE Computer Program	156
A-2	Flow Logic Diagram for HAC Computer Program	157
A-3	Flow Logic Diagram for LMCAP Computer Program	158
B-1	One Hour Weight Gain of Ta-W Alloys in Air	161

~~CONFIDENTIAL~~

~~DECLASSIFIED~~

0315587000
~~CONFIDENTIAL~~

ABSTRACT

To date, radioisotope fueled generators have utilized cylindrical fuel capsules, although spherical capsules are inherently stronger for the same wall thickness. Fabrication, assembly, and fueling techniques have been unavailable for spherical capsules. This program has developed these techniques. Superalloy and refractory metal spherical capsules have been fabricated to required tolerances. Full penetration crack-free welds have been achieved. Provisions for fueling such capsules remotely in a hot cell have been incorporated in the design. The validity of these provisions has been demonstrated by loading and then sealing simulated fuel into these capsules. Impact and creep tests are in progress.

The program was divided into the following three tasks:

- (1) Engineering analysis,
- (2) Development, fabrication, and assembly,
- (3) Impact, creep, and burst testing.

Twenty-nine spherical capsules were fabricated for testing. To date, ten of the 22 impact capsules have been tested. No containment violation has resulted at velocities to 560 ft/sec, the highest velocity attained. Testing at higher velocities is continuing. Burst pressures at failure were near predicted values. Creep testing has been initiated.

A spherical capsule parametric analysis was conducted to predict:

- (1) Burst pressure
- (2) Creep life to rupture
- (3) Critical impact velocities

Operating temperatures studied ranged from 1200°F to 1800°F. Terminal velocity and reentry conditions were established parametrically. Two inch diameter capsule designs were selected which were to be constructed of:

- (1) A Haynes-25 inner liner and Haynes-25 outer case for applications to 1500°F.
- (2) A Ta-10W inner liner and a Haynes-25 outer case for applications to 1800°F.

~~CONFIDENTIAL~~
0315587000

~~CONFIDENTIAL~~

The capsules were designed for a space application with a requirement of fuel dispersal at high altitude upon reentry from orbit. Estimated fuel release is about 190,000 ft. Impact velocity is estimated at 335 ft/sec. If the fuel capsule is raised to approximately 2500°F by aerodynamic heating due to an early abort, the sea level impact temperature will be about 500°F.

Two models have been developed to describe spherical capsule impact. A shear model has been developed which is applicable to thick walled spheres and a tension-compression model which can be applied to thin walled spheres. The behavior of the impacted spherical capsules was bracketed by the analytical predictions of the two models. Further work is deemed necessary to fully understand the impact mechanism. Such effort would lead to improved impact failure predictions.

The fuel capsules fabricated under this program are comprised of:

- (1) An inner liner for helium pressure containment
- (2) An outer shell for impact protection
- (3) A ring-shaped weld insert at the equator of the inner liner
- (4) A fuel retainer plate inside one of the inner liner hemispheres
- (5) Fuel simulant contained within one inner hemisphere and the retainer plate

The inner liner is designed so that virtually all fabrication, welding, testing, and inspection can be performed prior to fueling. Simulated fueling is accomplished by pouring fuel through a small hole and then welding a plug into the hole. This provides a sealed inner liner which can be subjected to decontamination prior to insertion into the outer shell. Outer shell closure is accomplished by circumferential TIG welding, and is compatible with existing hot cell procedures.

Seventy-six Haynes-25 hemispheres and 12 Ta-10W hemispheres were fabricated under this program. These were used to develop welding techniques and for testing. Preliminary welding techniques developed using flat plate specimens were later refined using hemispheres. Several

~~CONFIDENTIAL~~

031550700

~~CONFIDENTIAL~~

tools for testing and welding were also developed. A complete set of specifications for each of the welds required has been generated, and full penetration crack-free welds were consistently obtained. Typically, only a 0.001 to 0.005 inch buildup of fused metal was obtained on the weld surface. The welds and heat affected zone are as strong as the parent material. Welds of the outside shell were obtained with no melting on the inner liner sphere or fusion between the liner and shell.

The Spherical Capsule Program has demonstrated the superior structural impact characteristics of the thin wall spherical geometry. The necessary fabrication and welding techniques to permit use of radioisotope fueled capsules have been developed.

~~CONFIDENTIAL~~

031550700

~~CONFIDENTIAL~~
~~RECEIVED~~

I. SUMMARY

This program involved the design, development, fabrication, and test of spherical radioisotope capsules. Development of spherical capsules implies an advance in isotope capsule technology in terms of generator performance and safety. The developed capsules were designed independent of any particular isotope generator. Typical capsule requirements were used to constrain the capsule design. Two inch diameter capsule designs were developed for high and low temperature operation. The 1500^oF design utilizes two clads of Haynes-25. The 1800^oF design has a Ta-10W pressure containing inner liner and a Haynes-25 impact resistant outer shell. Both were designed to contain 60 watts(t) of plutonium dioxide microsphere fuel, with a 0.75 void fraction.

The program was divided in three tasks:

- (1) Engineering analysis,
- (2) Development, fabrication, and assembly,
- (3) Capsule impact, creep, and burst performance testing.

The engineering analysis task included:

- (1) Initial sizing studies to select the capsule design,
- (2) Aerodynamic analysis to evaluate capsule burnup characteristics,
- (3) Creep analysis including capsule volume and clad thickness changes with time,
- (4) Development of an advanced technique to more accurately describe impact,
- (5) Final test capsule design including components, assemblies, and tolerance studies.

The development, fabrication, and assembly task included:

- (1) Material procurement,
- (2) Component fabrication,
- (3) Welding and assembly development,
- (4) Impact capsule fabrication,
- (5) Burst and creep test specimen preparation.

- 1 -
~~CONFIDENTIAL~~
~~RECEIVED~~

~~CONFIDENTIAL~~

Creep, burst, and impact tests were performed in the third task. Impact testing was conducted at the Sandia Corporation for both Haynes-25/Haynes-25 and Haynes-25/Ta-10W capsules at various impact velocities above 325 feet per second. To date, ten of the twenty-two scheduled capsules have been impacted at velocities up to 560 feet per second with no containment violation.

The Haynes-25/Haynes-25 and Haynes-25/Ta-10W specimens have been burst tested. Measured burst pressures at failure were near predicted values.

Creep testing of two Haynes-25/Haynes-25 and two Haynes-25/Ta-10W capsules is being performed at Westinghouse Electric Corporation under Sandia Corporation contract.

All of the technical goals of the program have been met or exceeded. In addition, the capsule tests have demonstrated feasibility and attractiveness of spherical capsules.

~~CONFIDENTIAL~~

~~CONFIDENTIAL~~
~~REPRODUCTION~~

II. INTRODUCTION

This program was initiated in May 1966.* This report covers the entire program with the exception of:

- (1) Impact testing and evaluation of twelve capsules,
- (2) Creep testing and evaluation of four capsules.

A. Advantages of Spherical Capsules

A radioisotope fuel capsule must meet several constraints to be useful in an RTG system:

- (1) It should withstand terminal velocity impact on granite at its predicted impact temperature;
- (2) It must withstand the creep associated with high temperature operation and helium pressure buildup;
- (3) If fuel dispersal is required, the capsule wall must burn through and release the radioisotope at high altitude. If intact reentry is required, the capsule wall must withstand the increased temperature and pressure associated with reentry heating.

This program was conducted for a dispersal capsule concept.

The design constraints previously mentioned can be investigated individually. Figure II-1 shows the advantage of the spherical capsule when considering impact. The analysis depicted is based upon the "Water Model" where the kinetic energy of the impacting capsule is transformed into an equivalent compressive pressure. Note that on a comparative basis, the spherical capsule will withstand impact velocities more than 100 ft/sec higher than a comparable cylindrical capsule. The impact test results of this program have shown that spherical capsules withstand granite impact at velocities well above the terminal values. For example, all Haynes-25/Haynes-25

*U. S. Atomic Energy Commission Contract No. AT(29-2)-2072.

~~CONFIDENTIAL~~
~~REPRODUCTION~~

~~CONFIDENTIAL~~

capsules have successfully survived granite impact at velocities ranging from 360 to 560 ft/sec. The "Water Model" predicted failure at about 360 ft/sec. Conversely, the SNAP-9A tests showed an approximate correlation between cylindrical capsule "Water Model" predictions and impact experiments. The initial cylindrical capsule SNAP-19 tests resulted in weld failures well below the terminal velocity values. Testing of modified SNAP-19 designs incorporating hemispherical ends indicates improved impact capabilities. The test program has not progressed far enough so that complete conclusions can be drawn.

Figure II-2 shows a comparison of the sphere and cylindrical geometries based solely upon the creep characteristics. The creep life estimates are based upon using an extrapolated Larson-Miller parameter technique and calculating a percent of life expended in successive time increments. This method is described in detail in Section III-A. Note that for equivalent weight capsules, the spherical geometry enables operation at 100°F higher than the cylindrical fuel capsules. This advantage can also be expressed by taking a decreased weight at an identical operating temperature.

Figure II-3 is a summary giving a comparison of the spherical and cylindrical fuel capsules on an overall basis. This comparison is based upon the simultaneous satisfaction of the impact, creep, and reentry burn-through constraints. Note that for a given capsule weight, the spherical geometry provides a 100°F increase in operational temperature capability.

In summary, for the design constraints normally imposed on radio-isotope fuel containers, the spherical fuel capsule appears favorable with respect to a cylinder. Spherical capsule fabrication difficulties are of no greater magnitude than those associated with cylindrical capsules. Hemisphere components can be readily fabricated at relatively low cost. The cost of fueling and the complexity of assembly and welding operations are comparable for both geometries.

~~CONFIDENTIAL~~

~~CONFIDENTIAL~~
RESTRICTED

Figure II-1. Comparison of Impact Characteristics for Spherical Cylindrical Capsules

Figure II-2. Specific Power Comparison of Cylindrical and Spherical Capsules Based on Creep Alone

Figure II-3. Comparison of Three Inch Spherical and Cylindrical Capsules Based on Impact, Creep, and Burnup

~~CONFIDENTIAL~~
RESTRICTED

~~CONFIDENTIAL~~

B. Program Objectives

The primary objective of the program was to advance radioisotope encapsulation technology. The specific objectives of this phase included the design of a representative capsule and demonstration of its fabricability and performance characteristics.

1. Engineering Analysis and Design

a. Spherical Capsule Design Study. A comprehensive parametric design analysis was conducted. Objectives were to predict bursting pressure, creep life to rupture, and critical impact velocities for both Haynes-25/Haynes-25 and Haynes-25/Ta-10W capsule designs. Operating temperatures were varied over the 1200°F-1800°F temperature range. The total creep that occurs in six and nine months was specified.

b. Parametric Aerodynamic Study. A parametric aerodynamic study was conducted to establish aerodynamic characteristics of spherical capsules. This included terminal velocity and reentry heating calculations. Fuel release altitudes were determined at various altitudes and velocities. Radii and wall thicknesses were varied for both the Haynes-25/Haynes-25 and Haynes-25/Ta-10W capsules. Terminal velocities were calculated for spherical capsules of various weights and diameters.

c. Design Selection. The most promising designs for a Haynes-25/Haynes-25 and a Haynes-25/Ta-10W were specified after the studies.

d. Mechanical Design. Mechanical design studies were conducted after selection of the overall high and low temperature spherical capsule configurations. Layout drawings showing weld configurations were prepared.

2. Capsule Development, Fabrication, and Assembly.

Using the information generated in Task 1.0, a systematic fabrication development program was defined. Detailed assembly and welding procedures for both the high and low temperature capsule designs were specified. Fabrication and welding studies were performed which led to the achievement of sound, full penetration weld joints. Twenty-nine capsules were fabricated for the test program conducted by Sandia.

~~CONFIDENTIAL~~

~~CONFIDENTIAL~~
DECLASSIFIED

3. Performance Testing

a. Impact Testing. Impact testing at various velocities was performed on Haynes-25/Haynes-25 and Haynes-25/Ta-10W capsules. Post test diagnostics were conducted.

b. Creep Testing. Creep testing on two Haynes-25 and two Ta-10W capsule liners is in progress.

c. Burst Testing. Burst tests of two Haynes-25 and one Ta-10W capsule liners were conducted.

Most of the technical objectives of the program have been achieved. The only exceptions are tests which are still in progress. In some cases, additional effort was performed. For example, 29 specimens were fabricated for capsule testing instead of the 22 originally planned.

The following is the allotment of the 29 test specimens:

Impact Testing	14 Haynes-25/Haynes-25
	8 Haynes-25/Ta-10W
Creep Testing	2 Haynes-25
	2 Ta-10W
Burst Testing	2 Haynes-25
	1 Ta-10W

C. Design Criteria

Where possible, the design criteria were selected using current radioisotope thermoelectric generator (RTG) technology. These sections are defined in the following subsections.

1. Radioisotope Fuel

Plutonium-238 (Pu-238) microspheres were selected based upon their use in the SNAP-19 and SNAP-27 systems currently under development.

2. Capsule Lifetime

Five years was selected as the capsule design creep to rupture time at operating temperature and pressure. Deep space probes which will

-7-
~~CONFIDENTIAL~~
DECLASSIFIED

~~CONFIDENTIAL~~

require RTG power systems with operating lifetimes of this duration are being planned.

3. Reentry Safety

High altitude release and dispersal of the PuO_2 microspheres was selected as the reentry safety mode. A capsule designed to this criterion remains flexible in that a protective (ablative) material can be provided for intact reentry.

4. Launch Abort Safety

To meet nuclear safety guidelines, the capsule must be designed to withstand terminal velocity impact on granite and provide complete containment in the event of an early launch abort.

5. Capsule Operating Temperature

Either a PbTe or SiGe thermopile with radiative thermal coupling of the fuel capsule to the thermopile can be used in an RTG. Temperatures of 1500°F and 1800°F were selected for these requirements.

Several design constraints were set by standard operating procedures of encapsulating large quantities of radioisotope. Double fuel encapsulation was used to facilitate decontamination. A 0.020 inch minimum wall thickness was selected. Although this could probably be reduced, it would require development effort at the fuel encapsulating facility.

The last major a priori design constraint is capsule material selection. Haynes-25 was selected as the inner liner for the lower temperature (1500°F) capsule and Ta-10W for the higher temperature (1800°F). Haynes-25 was selected as the outer shell for impact and oxidation protection in both cases. These selections were based upon materials compatibility, workability, weldability, and strength at operating temperature.

~~CONFIDENTIAL~~

~~CONFIDENTIAL~~
DECLASSIFIED

III. SPHERICAL CAPSULE ANALYSIS

A. Initial Sizing

A parametric sizing study was conducted. The inner liner was used for pressure buildup and the outer shell for terminal velocity impact. Thicknesses were determined over a range of capsule sizes, fuel loadings and operating temperatures. The study was conducted with the aid of a digital computer program (CAPSPE) written for this contract.

Spherical capsule analysis can be divided into two categories:

- (1) Pressure buildup evaluation,
- (2) Impact evaluation.

The Larson-Miller technique was used to establish the inner liner thickness requirements to withstand the helium pressure buildup associated with the alpha emitting radioisotope. The failure mode of an alpha emitting radioisotope fueled capsule is creep failure, the result of sustained material stress at elevated temperature for a long time. Although the stress at any given time is well below the quoted yield stress, the slow creep action eventually ruptures the capsule. As a rule of thumb, this failure phenomenon is possible when the operating temperature is in excess of one-third the melting temperature of the material. Below this temperature, normal stress-temperature relationships can be used.

The Larson-Miller approach is an empirical technique which predicts material failure under a constant pressure-temperature condition. It can be applied to transient conditions by using small time increments. Based upon the computed containment time, a value known as the "percent life used" is calculated for the time step. The procedure is repeated for each advance in time while summing the "percent life used". When the "percent life used" reaches one hundred percent, capsule failure is assumed.

The impact analysis selected for the preliminary designs is commonly referred to as the "Water Model". This assumes transformation of the impact energy into an equivalent (hydrostatic) pressure.

~~CONFIDENTIAL~~
DECLASSIFIED

0311508700

~~CONFIDENTIAL~~

The analysis model is shown in Figure III-1. The capsule consists of two containment structures. The inner liner is used as the pressure containment structure, while the outer shell is used for oxidation and impact protection. It should be noted that 50 percent of the inner liner's wall thickness was assumed to contribute to the capsule's impact resistance. The helium generated within the fuel is assumed to be completely released to within the inner liner.

Figure III-1. Spherical Capsule Analytical Model

0311508700

~~CONFIDENTIAL~~

~~CONFIDENTIAL~~
REF ID: A66311

Calculations are initiated by assuming an inner liner wall thickness and an end of mission temperature. Temperature during the mission can be approximated by:

$$T = T_e e^{-\frac{\lambda \tau}{4}} \quad (\text{III-1})$$

where:

T_e = beginning of life capsule temperature
 λ = 0.693/half-life of the fuel
 τ = time

The 1/4 in the exponential term is an approximation for radiation heat transfer.

The ideal gas law is valid for helium at the pressure and temperature levels under consideration. Hence, pressure can be computed by:

$$P_i = \frac{\rho_f (1 - e^{-\lambda \tau}) RT (1 - X_v)}{M X_v} \quad (\text{III-2})$$

where:

P_i = pressure
 ρ_f = radioisotope fuel density (fuel form)
 R = universal gas constant
 X_v = void fraction (volume contained by the inner liner, but not containing fuel)
 M = fuel molecular weight

Thin wall theory can be used for the pressure vessel stress calculations if the wall thickness is not greater than ten percent of the inside capsule radius. Based on this assumption, the induced hoop stress can be obtained from:

$$S = \frac{P_i R_{fc}}{2 t_{fc}} \quad (\text{III-3})$$

where:

S = stress
 R_{fc} = inner layer radius
 t_{fc} = wall thickness

~~CONFIDENTIAL~~
REF ID: A66311

CONFIDENTIAL

A Larson-Miller parameter (PAR) may be defined by:

$$\text{PAR} = T (b + \log_{10} \tau_c) (10^3) \quad (\text{III-4})$$

where:

τ_c = containment time
b = constant

Rearranging:

$$\tau_c = 10 \left[\frac{\text{PAR} \times 10^3}{T} - b \right] \quad (\text{III-5})$$

Since the temperature and pressure of a capsule containing an alpha emitting fuel is continuously changing, this equation is applied as an input in a forward difference technique. Based on the known containment time, a term known as "percent life used" is calculated from:

$$\text{ELU} = \frac{100 \Delta \tau}{\tau_c} \quad (\text{III-6})$$

where:

ELU = percent life used
 $\Delta \tau$ = time increment
 τ_c = total containment time

The above procedure is repeated for each advance in time. The values of "percent life used" are summed until the value is equal to one hundred percent. The time then represents containment time for the thickness under consideration. The containment time is then compared to the mission life-time. The wall thickness is either increased or decreased and the entire procedure is repeated until mission time is equal to containment time.

The volume of the radioisotope fuel can be computed by:

$$V_f = \frac{4\pi}{3} (R_{fc} - t_{fc})^3 (1 - X_v) \pi \quad (\text{III-7})$$

CONFIDENTIAL

~~CONFIDENTIAL~~

The power level is then:

$$Q_b = (Pd) (V_f) \quad (\text{III-8})$$

or:

$$Q_e = Q_b e^{-\lambda \tau_e} \quad (\text{III-9})$$

where:

- Q_b = beginning of life power level
- Q_e = end of life power level
- Pd = power density of the fuel
- τ_e = end of mission time

The weight of both the fuel and pressure vessel can be computed by:

$$W_f = \rho_f V_f \quad (\text{III-10})$$

and

$$W_{fc} = \frac{4}{3} \pi \left[R_{fc}^3 - (R_{fc} - t_{fc})^3 \right] \rho_{fc} \quad (\text{III-11})$$

where:

- W_f = weight of the fuel
- ρ_f = density of the fuel
- W_{fc} = weight of the pressure vessel
- ρ_{fc} = density of the pressure vessel

The weight of the outer shell is:

$$W_{fcs} = \frac{4}{3} \pi \left[(R_{fc} + t_{fcs})^3 - R_{fc}^3 \right] \rho_{fcs} \quad (\text{III-12})$$

where:

- W_{fcs} = weight of outer shell
- t_{fcs} = outer shell wall thickness
- ρ_{fcs} = density of outer shell material

~~CONFIDENTIAL~~

DECLASSIFIED

CONFIDENTIAL

Neglecting the gap between the inner liner and outer shell (which introduces only a small error), the total weight of the capsule is:

$$W_t = W_{fcs} + W_{fc} + W_f \quad (\text{III-13})$$

The bulk density of the capsule is:

$$\overline{W} = \frac{3 W_t}{4\pi (R_{fc} + t_{fcs})^3} \quad (\text{III-14})$$

The capsule drag coefficient now can be obtained from Figure III-2 (Reference 3). The impact or terminal velocity is:

$$V_t = \sqrt{\frac{2g W_t}{\rho_{air} C_D A_{ref}}} \quad (\text{III-15})$$

where:

- V_t = impact velocity
- C_D = drag coefficient
- A_{ref} = capsule reference (cross section) area
- ρ_{air} = air density
- g = gravitation constant

According to the "Water Model", the outer shell wall thickness is:

$$t_{fcs} = \frac{P_v R_{fcs} F}{2 S_u} \quad (\text{III-17})$$

where:

- P_v = equivalent impact pressure
- S_u = ultimate tensile stress
- F = safety factor

The full inner liner thickness cannot be assumed effective against impact since it must withstand creep subsequent to impact. However, it contributes to the overall impact resistance of the capsule. Therefore, 50 percent of the thickness was assumed effective for impact resistance. Impact characteristics are influenced by helium pressure at the time of impact.

CONFIDENTIAL

~~CONFIDENTIAL~~ REPRODUCED

Figure III-2: Sphere Drag Coefficient, C_D

~~CONFIDENTIAL~~ REPRODUCED

0315587030
~~CONFIDENTIAL~~

However, the internal helium pressure is negligible relative to typical impact "pressures" (P_v) and the effect is insignificant.

The capsule analysis has been programmed for use on the UNIVAC-1108 digital computer utilizing FORTRAN IV. The flow logic diagram is presented in Appendix A.

The program was used for a parametric study. Results using Ta-10W as the inner liner are summarized in Figures III-3 through III-5 for an end of life capsule temperature of 1800°F. These show the liner thickness and terminal velocities. A minimum wall thickness of 0.020 inch was imposed because of fabrication and tolerance limits. Since the parametric design study contained a number of minimum thickness designs, lower temperatures were not investigated.

A similar parametric study was conducted for the Haynes-25/Haynes-25 capsule configuration at 1200, 1500, and 1800°F. The results for the 1500°F case are shown in Figures III-6 through III-10.

1. Selection of the Index Capsule

The index capsule's diameter was selected at two inches. For the Haynes-25/Haynes-25 capsule, a void fraction of 0.750 leads to a maximum specific power (watts(t)/lb). The Haynes-25/Ta-10W outer diameter and fuel loading were chosen to correspond to the Haynes-25/Haynes-25 capsule to simplify capsule fabrication and lower fabrication costs. Selection of the 2.00 inch diameter and 0.750 inch void fraction constrain thermal power to 60 w(t). This is a reasonable power level for a typical low powered RTG fuel capsule.

Table III-1 summarizes the characteristics of the index capsules. All subsequent analyses documented in this report are based on these. Although the computed wall thicknesses of the Haynes-25 outer shell and inner liner vary slightly with the high and low temperature designs, as shown in Table III-1, the Haynes-25 walls were standardized at a single thickness of 0.034 inch. This thickness is within ± 0.005 inch of all the calculated thicknesses and allows purchase of a single sheet thickness.

0317281030
~~CONFIDENTIAL~~

CONFIDENTIAL

- 17 -

Figure III-3. Ta-10W Pressure Vessel Thickness Required to Withstand He Pressure vs. Capsule Diameter

Figure III-4. Outer Shell Thickness vs. Diameter for Haynes-25/Ta-10W Capsule

CONFIDENTIAL

CONFIDENTIAL

CONFIDENTIAL

Figure III-5. Terminal Velocity vs. Diameter for Haynes-25/Ta-10W Capsule

CONFIDENTIAL

CONFIDENTIAL

Figure III-6. EOL Thermal Power vs. Diameter for Haynes-25/Haynes-25

Figure III-7. Weight vs. Diameter for Haynes-25/Haynes-25 Capsule

Figure III-8. Haynes-25 Pressure Vessel Thickness Required to Withstand He Pressure vs. Capsule Diameter

Figure III-9. Outer Clad Thickness vs. Diameter for Haynes-25/Haynes-25 Capsule

~~CONFIDENTIAL~~

~~UNCLASSIFIED~~

Figure III-10. Terminal Velocity vs. Diameter for Haynes-25/Haynes-25 Capsule

~~CONFIDENTIAL~~

~~UNCLASSIFIED~~

0315507030

~~CONFIDENTIAL~~TABLE III-1. SPHERICAL CAPSULE DESIGN SPECIFICATIONS

Capsule Material	Haynes-25/Haynes-25	Haynes-25/Ta-10W
Creep Lifetime	5 Years	5 Years
Surface Operating Temperature	1500°F	1800°F
Outer Shell		
Outer Diameter	2.005 Inches	2.005 Inches
Inner Diameter	1.937 Inches	1.937 Inches
Inner Liner		
Outer Diameter	1.925 Inches	1.925 Inches
Inner Diameter	1.857 Inches	1.885 Inches
Fuel Source	$^{238}\text{PuO}_2$	$^{238}\text{PuO}_2$
	Microspheres	Microspheres
Thermal Power Level	60 Watts	60 Watts
Encapsulated Weight	0.55 Pound	0.60 Pound

B. Aerothermodynamic Analysis

The aerothermodynamic analysis of the spherical fuel capsule covered aerodynamic and thermal calculations. An aerodynamic study was performed to generate trajectories and aerodynamic heating rates for various configurations.

The thermal study was performed to establish capsule performance under aerodynamic heating and terminal cooling conditions. The model developed was used to predict burnup altitudes, partial burnup* zones, and capsule temperature history during the reentry and terminal phase of the flight. In addition, this model was used to predict the temperature to which static capsules must be heated in the impact test program to meet the desired impact temperature requirements.

*Partial burnup occurs when the protective case has been partially burned away to expose some of the fuel, but the fuel has not been dispersed, and the capsule impacts on the earth in this condition.

0317281934

~~CONFIDENTIAL~~

~~CONFIDENTIAL~~

~~DECLASSIFIED~~

1. Aerodynamic Results

Based upon the aerothermodynamic analyses performed, no major problem areas have been identified. The thin walled capsule is subjected to high heating rates as expected, and burns up for all likely methods of reentering the earth's atmosphere from earth orbit missions.

Partial capsule burnup is confined to a narrow zone while sea level impact of an intact capsule occurs at a velocity below the limiting value.

A computerized thermal model of the capsule has been developed. Thermal analyses have been performed to define temperature variations throughout the capsule for reentry heating and for two cooling conditions.

a. HAC Computer Program. Reentry trajectories and aerodynamic heating rates have been defined by the Hittman Aerodynamic Code (HAC),* a digital computer program. This technique utilizes a drag coefficient and heating rate which are dependent upon the flow regime (free molecular, continuum or subsonic). Forty-two runs have been made in support of thermal analyses and parametric aerodynamic studies.

The HAC program begins at specified initial altitude, velocity, and reentry angle and solves the equations of motion simultaneously by the Runge-Kutta difference technique. All output parameters are calculated as a function of time, and in addition, the aerodynamic heat flux is integrated over the reentry heating period. This is used to rapidly evaluate the partial burnup zone.

b. Selection of Aerodynamic Parameters. The initial analytical effort did not have a defined configuration and a parametric approach was used to generate trajectory and heating data. Runs were made for capsule diameters of 1.0, 3.0, and 5.0 inches and average capsule specific weights of 0.15, 0.2, 0.25, 0.3 and 0.35 lbs/in³. The primary purpose was to provide the heating data shown in Figures III-11, III-12, and III-13.

*A Flow Logic Diagram of the HAC Code is presented in Appendix A.

~~CONFIDENTIAL~~

~~DECLASSIFIED~~

Figure III-11. Stagnation Point Heating Rate for One Inch Sphere

Figure III-12. Stagnation Point Heating Rate for Three Inch Sphere

Figure III-13. Integrated Stagnation Point Heat Flux vs. Capsule Diameter

~~CONFIDENTIAL~~

Two conditions have been considered in detail, reentry from orbit and an abort during ascent. In both cases, SNAP-19 data obtained from References 1 and 2 have been used as a guide in defining the initial capsule trajectory parameters. (Figure III-17, presented later, shows the nominal ascent trajectory characteristics used in this study.)

Release of the capsule following orbital decay from 400,000 feet has been assumed to take place at 283,000 feet with a velocity of 25,200 ft/sec and an angle with the horizontal of -1.12° . This reentry condition is plausible and results in only a slightly lower heat flux to the sphere than release at 400,000 feet.

Hypersonic drag coefficients and other physical data on the spheres are shown in Table III-2.

c. Aerodynamic Heating Rates. All heating rates used in the thermal analysis are results from the HAC program and, with only a few exceptions, are continuum flow regime heating rates calculated by:

$$\dot{q} = K(17600) \left(\frac{1}{RN}\right)^{1/2} \left(\frac{\rho}{\rho_o}\right)^{1/2} \left(\frac{V}{V_c}\right)^{3.15} \quad (\text{III-18})$$

where:

RN	=	characteristic nose radius
K	=	heating coefficient relative to stagnation point
$\dot{q}$	=	stagnation point heating rate
ρ	=	air density
ρ_o	=	sea level air density
V	=	velocity
V_c	=	26,000 ft/sec

The result magnitudes presented in Figures III-11, III-12, and III-13 suggest that a thin walled spherical capsule will burn up rapidly regardless of whether the sphere is stabilized or heated uniformly. Figure III-13 indicates the sphere heating rate is a strong function of sphere density rather than diameter. Final results for the two inch sphere are shown in Figures III-14 and III-15. Little difference exists between the two final configurations. Peak heating is delayed to lower altitude for the abort case

~~CONFIDENTIAL~~

TABLE III-2. AERODYNAMIC AND PHYSICAL DATA USED IN ANALYSIS OF TWO INCH SPHERES

Capsule	Outer Diam. (ft)	Wt. (lbs)	Cross Section Area (ft ²)	Drag Coefficient		Outer Shell Thick. (in)	Inner Liner Thick. (in)	Gap	Cont. Bal- listic Co- efficient (lbs/ft ²)
				Free Mole- cule Flow	Cont. Flow				
Haynes- 25/ Ta-10W	0.167	0.626	0.02185	2.0	0.92	0.035	0.020	0.005	31
Haynes- 25/ Haynes- 25	0.167	0.588	0.02185	2.0	0.92	0.30	0.038	0.005	29

~~CONFIDENTIAL~~

~~CONFIDENTIAL~~

CONFIDENTIAL

Figure III-14. Capsule Diameter Trajectory and Heating Rate for Two Inch Sphere for Release at 283,000 Ft.

Abort and Release at 218 Seconds After Liftoff

Figure III-15. Trajectory and Heating Rate for Two Inch Sphere Following Abort

CONFIDENTIAL

0315587000
~~CONFIDENTIAL~~

presented in Figure III-15. These abort cases will be discussed later, but an abort at 218 seconds after booster liftoff is emphasized. This is the most probable abort estimated to come close to partial rather than total burnup. Although Main Engine Cut Off (MECO), or abort at 218 seconds, leads to total burnup even with uniform heating, the results are readily extrapolated to the nearby partial burnup cases.

d. Terminal Velocity Calculations. Terminal velocities of spheres are shown parametrically in Figure III-16. The velocities were calculated by using an iterative technique with:

$$V_{\text{Terminal}} = \left(\frac{8rw}{3C_d\rho} \right)^{1/2} \quad (\text{III-19})$$

where.

- r = sphere radius
- w = sphere average specific weight
- ρ = atmospheric mass density
- C_d = drag coefficient determined from Reference 3 as a function of both Reynolds number and Mach number

The data are for smooth spheres having a C_d of at least 0.2. The abrupt change in terminal velocity between a diameter of one inch and three inches is due to the critical Reynolds number phenomenon shown in Figure III-2. The one inch sphere does not possess a critical Reynolds number. The low C_d on the three inch sphere is due to boundary layer separation on the back side. Since pressure drag is predominant for the subsonic sphere, rearward movement of the separation point has a marked effect. For the two inch Haynes-25/Ta-10W sphere, sea level terminal velocity is 335 ft/sec. Trajectories constructed as part of the reentry heating study verified that the spheres will decelerate to the terminal velocity.

e. Sphere Stability. Sphere stability is important since it affects the aerodynamic heating distribution. The spherical fuel capsules are not loaded uniformly and the center of pressure (CP) and center of gravity (CG) are not coincident. This gives a dynamic system that is statically stable, but free to tumble or oscillate about the CG. Release of the sphere from the

0317201000
~~CONFIDENTIAL~~

~~CONFIDENTIAL~~

Figure III-16. Terminal Velocity of Spherical Capsules

~~CONFIDENTIAL~~

RTG may cause initial rotation about the tumbling axis. A tumbling analysis is necessary to obtain the altitude at which the initial tumble energy is reduced to zero by aerodynamic damping forces. A number of tumbling analyses of this type have been performed (see, for example, Reference 4). Hittman Associates (Reference 5) presents the following equation which is directly applicable:

$$h_d = \frac{1}{\beta} \ln \frac{2\rho_t A L^3 C_{ms}}{I (\dot{\theta} L/V)^2} \quad (\text{III-20})$$

where:

- h_d = stabilization altitude defined as the end of tumbling - ft
- t = atmospheric constant of 0.156 slugs/ft³
- $\dot{\theta}$ = initial tumble rate - rad/sec
- β = atmosphere constant = $\frac{1}{17,150 \text{ ft}}$
- V = initial velocity 25,000 ft/sec
- I = moment of inertia about tumbling axis - lb-sec²-ft
- A = cross section area - ft²
- C_{ms} = static moment of coefficient
- L = distance between CP and CG - ft

~~CONFIDENTIAL~~
UNCLASSIFIED

This has been used for the two inch Haynes-25/Ta-10W sphere assuming that the CP is at the center of the sphere and with the following data:

$$\begin{aligned} A &= 0.0218 \text{ ft}^2 \\ L &= 0.0416 \text{ ft} \\ \dot{\theta} &= 10 \text{ rev/sec} - 63 \text{ rad/sec} \\ I_{cg} &= 8.53 \times 10^{-5} \text{ lb-sec}^2\text{-ft} \end{aligned}$$

The calculated stabilization altitude, h_d , is 190,300 feet. Although the equation contains many assumptions, impact with $\dot{\theta}$ greater than zero appears possible. Consequently, aborts along the ascent trajectory can result in a stabilized or tumbling mode during the ensuing aerodynamic heating period.

2. Thermal Analysis

a. Partial Burnup Analysis. SNAP-19 data from References 1 and 2 have been used as the nominal ascent trajectory. Some of these data are shown in Figure III-17 (and in Figure III-26).

The capsule was assumed to possess the properties at time of abort defined by Figure III-17. Although explosion or release will impart an incremental velocity to the capsule, it is negligible compared to its velocity along the trajectory.

b. TAP-3 Computer Code. A transient model capable of analyzing a two dimensional object having variable diameter, shell thickness, material properties and heating is required. This requires a computer program. We used the TAP-3 program with a UNIVAC-1108 digital computer (Reference 6). TAP-3 uses a network of conductors and capacitors to describe heat transfer. Its application requires definition of a nodal arrangement and designation of built-in arithmetic functions and subroutines which describe the boundary conditions or other special problem features such as heating rates or ablation.

c. Thermal Model Description. The spherical fuel capsule thermal model is shown in Figures III-18 through III-20. It contains 53 nodes; the first 51 being within the capsule, 52 the space environment at 0°R , and 53 the ambient air during terminal cooling of the sphere. Most of the thermal analysis has used the 52 node model setup for aerodynamic heating into the sphere. The model with node 53 has been used for terminal cooling estimates

~~CONFIDENTIAL~~
UNCLASSIFIED

Figure III-17. Nominal Ascent Trajectory

CONFIDENTIAL

Figure III-18. Spherical Capsule Two-Dimensional Model

CONFIDENTIAL

03150134
~~CONFIDENTIAL~~

Nodes 1-32 Outer Shell
 Nodes 33-40 Inner Shell
 Nodes 41-51 Fuel
 Node 52 Space at 0°R
 Node 53 Ambient Air for Cooling

Stagnation Flow
 for Stable Sphere

Figure III-19. Thermal Model Nodal Arrangement

03171278
~~CONFIDENTIAL~~

Note: As exterior nodes ablate, additional admittances not shown are used to connect nodes 9 - 40 with radiation node 52.

Node 53 is only included for convective cooling problems.

Figure III-20. Spherical Capsule Thermal-Electrical Analog

0315547030

~~CONFIDENTIAL~~

and to determine the transient impact temperature for test purposes. The Haynes-25/Ta-10W and the Haynes-25/Haynes-25 configurations use the same model, differing only in a few input constants. The important characteristics of the thermal model are:

- (1) A 1/8 section of a sphere, shown in Figure III-18, represents the selected thermal model. Interior plane surfaces are assumed to be insulated and the fuel extends to the meridian planes of symmetry. Since the model is intended for short duration high heat pulses, the hemisphere not containing fuel is neglected;
- (2) Following release from the RTG, the fuel capsule is assumed to be stable (fuel forward) or tumbling in a manner that produces uniform heating. Heating rate and distribution depends on stability, so the approach has been to look at the highest and lowest heating rates on the premise that these analyses will bracket the real case. The initial results have justified this approach;
- (3) The outer shell is divided into four thicknesses of material radially, with eight cuts in the circumferential direction, giving a total of 32 nodes in the outer shell. Throughout, the model conduction is both radial and circumferential as Figures III-19 and III-20 imply;
- (4) The inner liner consists of eight nodes and is separated from the outer shell by a helium filled gap;
- (5) The capsule outer surface radiates to the surrounding environment (assumed to be space at 0°R). Radiation heat transfer between a node and space is dependent upon whether the node exterior to it has ablated. For example, the radiation between node 16 and space is zero until node 1 has ablated (see Figure III-19);

0315547030

~~CONFIDENTIAL~~

~~CONFIDENTIAL~~

- (6) In the same manner, aerodynamic heating to node 16 is zero until node 1 has ablated,
- (7) The radioisotope microsphere thermal conductivity is assumed to be the value of solid fuel;
- (8) Convective cooling during the terminal trajectory takes place through admittances from nodes 1 through 8 and an adjusted ambient air temperature;
- (9) The physical model shown in Figure III-19 is adapted to the TAP-3 code through the electrical analog of Figure III-20. All Y's are admittances defined as $\left(\frac{kA}{l}\right) \frac{\text{Btu}}{\text{sec-}^{\circ}\text{F}}$. Each node, except for 52 and 53, has a capacitance defined as $WC_p \frac{\text{Btu}}{\text{sec}}$.

A 2.2 inch sphere was used for the first thermal model computer runs. However, since the time to burnup for orbital decay cases is short, the results of these runs (shown in Figures III-21 and III-22) are applicable to a 1.0 inch sphere as well. (Shell thicknesses studied were the same for 2.0 inch and 2.2 inch capsules.) The data on Figure III-21 are for a stable capsule released at 283,000 feet. Referencing Figure III-14 gives an approximate idea of the heat flux applied and the reason that the time until the inner liner is exposed is so small. Computer calculations were terminated when the Ta-10W inner liner reached 3800°F. Oxidization of the Ta-10W material occurs very rapidly at elevated temperatures. The material removal rate is sufficiently rapid to assume that the fuel microspheres are released and dispersed if the Ta-10W liner is exposed anywhere along the positive slope of the aerodynamic heating curve. The tantalum oxidization rate has been reported in Reference 7 where an empirical expression for recession rate is derived. An extension to this analysis has been performed for Ta-10W and is included in Appendix B. The significant result is an equation for the recession rate of Ta-10W:

$$\frac{\Delta L}{\Delta \theta} \frac{\text{inches}}{\text{sec}} = 0.00504 \Delta X_o \left[\frac{P_{t2}}{r_e} \right]^{1/2} \text{ for } T > 3800^{\circ}\text{F} \quad (\text{III-21})$$

~~CONFIDENTIAL~~

~~CONFIDENTIAL~~

Figure III-21. Temperature Transient for 2.2 Inch Sphere with Stagnation Heating After Orbital Decay

Figure III-22. Temperature Transients for 2.2 Inch Sphere with Uniform Heating After Orbital Decay

~~CONFIDENTIAL~~

~~CONFIDENTIAL~~
~~CONFIDENTIAL~~
~~CONFIDENTIAL~~

where:

ΔX_o = mass fraction of oxygen in gas
 P_{t_2} = total pressure behind normal shock wave in lb/ft²
 r_e = effective nose radius in feet

Substitution of appropriate values shows that the recession rate of the exposed Ta-10W liner is about 0.04 inch/second. The Ta-10W liner will, therefore, vanish within a few seconds after the Haynes-25 shell is breached.

Release of a 2.2 inch capsule at 283,000 feet, with uniform heating, also results in rapid capsule burnup as shown in Figure III-22. Fuel microspheres are exposed approximately 20 seconds after capsule release. The aerodynamic heating at this point is still far short of its peak. At this point in the analysis, it was concluded that further work must center on relatively early abort cases. Releases at later points along the launch cycle result in burnup.

Figure III-23 presents the results for the final Haynes-25/Ta-10W configuration assuming the lowest heating (uniform) rate and release at 218 seconds.* Fuel release begins about 296 seconds from time of abort and occurs on the positive slope of the aero heat rate curve in Figure III-15. The altitude at the initiation of fuel dispersal is 145,000 feet. Resulting temperature profiles through the fuel capsule are shown in Figure III-24. The drop in temperature after capsule release is due to radiation without heating.

Figure III-25 is a similar analysis for the final Haynes-25/Haynes-25 configuration, again with uniform heating. Fuel release is estimated to begin at 305 seconds from time of abort. The altitude at start of fuel dispersal is about 110,000 feet. Note from Figure III-15 that the dispersal occurs just about at peak heating so this case is approaching the partial burnup zone.

d. Partial Burnup Analysis. Partial burnup was defined earlier as the zone where some protective shell material is burned off the capsule and the

* The trajectory and heating data for this case are shown in Figures III-15, III-17, and III-26.

~~CONFIDENTIAL~~
~~CONFIDENTIAL~~
~~CONFIDENTIAL~~

~~CONFIDENTIAL~~

Figure III-23. Temperature Transients for 2.0 Inch Haynes-25/Ta-10W Configuration

Figure III-24. Temperature Distribution for Haynes-25/Ta-10W Sphere

Figure III-25. Temperature Transients for 2.0 Inch Haynes-25/Haynes-25 Capsule

~~CONFIDENTIAL~~

~~CONFIDENTIAL~~
~~REPRODUCED~~

fuel is exposed but not totally dispersed. This zone is shown in Figure III-26. The upper end was determined by:

- (1) From Figure III-25, the time was determined at which fuel was exposed for the Haynes-25/Haynes-25 capsule;
- (2) Using the time from Item (1), the area was determined under the appropriate heating curve in Figure III-15. This is the heat which results in burnup;
- (3) Comparing the integrated heat input computed by HAC runs with the heat determined in Item (2) to determine which trajectory will produce the required total heat for a tumbling capsule.

The result is plotted on Figure III-26. Similar reasoning was used to establish the lower end of the zone except that this constraint is caused by a Haynes-25/Ta-10W sphere with stagnation heating.

The most significant result of the burnup analysis is that partial burnup of the two inch fuel capsule will occur for aborts between 135 and 186 seconds of the assumed nominal launch trajectory. For the booster chosen (Thorad/Agenda D), abort during this time period has a much lower probability than at points such as eject booster and main engine cutoff. Although each booster/RTG combination must be evaluated separately, the spherical capsule combinations other than the one evaluated probably will result in a similarly narrow partial burnup zone.

e. Terminal Temperature Analysis. The thermal model produced to evaluate cooling of an intact spherical capsule during a terminal trajectory. The largest source of error is the convection cooling coefficient. Reference 8 has been used as a guide in this analysis. Most data indicate that the following relation can be used to approximate the heat transfer process.

$$Nu = 0.33 (Re)^{0.6} \quad (III-22)$$

~~CONFIDENTIAL~~
~~REPRODUCED~~

CONFIDENTIAL

CONFIDENTIAL

Figure III-26. Burnup Zones for Two Inch Capsule

~~CONFIDENTIAL~~

where:

Nu = Nusselt number = $\frac{hD}{k}$
Re = Reynolds number = $\left(\frac{Dv\rho}{\mu}\right)$
h = mean convective coefficient for the sphere
D = sphere diameter
k = mean air conductivity
v = sphere velocity
 ρ = air density
 μ = air kinematic viscosity

Using this equation with known trajectory and atmospheric conditions allows the mean heat transfer coefficient, h, to be calculated as a function of time. A two inch Haynes-25/Ta-10W sphere was assumed with an initial outer shell temperature of 2500°F and a temperature distribution as shown in Figure III-27 for time zero at 70,000 feet. The calculated results are shown in Figure III-28. Figure III-28 contains three curves of node 4 temperatures (node 4 being the point on the surface most desirable to evaluate because of local impact stresses) to show the effects of varying h. The upper curve is for h = 30 Btu/ft²-hr-°F while the lower curves were generated by use of two different Nusselt number - Reynolds number equations as indicated. The middle curve ($h_{avg} \sim 70$ Btu/ft²-hr-°F) probably is the most reasonable estimate. This gives an impact temperature of 430°F. This temperature does not include the small effect of material deformation at impact; however, it is a suitable initial condition for impact testing.

Additional calculations have been made for the Haynes-25/Ta-10W configuration to estimate outer shell equilibrium temperatures for several mean convective cooling coefficients. These results are given in Table III-3.

~~CONFIDENTIAL~~

~~CONFIDENTIAL~~

Solid Line Is For Haynes-25/Ta-10W Configuration and Corresponds to Figure III-26 with $h \approx 70$. Capsule Is Stabilized with Node 1 at Stagnation Point

Figure III-27. Terminal Temperature vs. Capsule Radius

~~CONFIDENTIAL~~

Figure III-28. Terminal Temperature Results for Two Inch Sphere

~~CONFIDENTIAL~~

TABLE III-3. SPHERICAL FUEL CAPSULE EQUILIBRIUM
TEMPERATURES UNDER CONVECTIVE COOLING

<u>Convective Coefficient (Btu/ft²-hr-°F)</u>	<u>Steady State Exterior Surface Temperature (°F)</u>
30	280
86.5	137
110	120

In the steady state case with $h = 86.5$, about 10°F difference exists between the inner liner and outer shells. At impact following a terminal trajectory, this same difference is estimated as 75°F and is shown in Figure III-27.

These data were not verified by computer runs since the temperatures were very low.

f. Impact Test Temperature Transient. A time period occurs between heating cutoff and capsule impact. Therefore, a transient thermal analysis was performed to predict the capsule temperature required prior to impact to meet the desired impact temperature. It was based upon the following data:

Sphere Dimensions

Outer diameter	= 2 inches
Haynes-25 outer shell thickness	= 0.035 inch
Ta-10W inner liner thickness	= 0.020 inch
Mean gap between shells	= 0.005 inch

Simulated Fuel Properties

ρ	= 0.3 lbs/in ³
C_p	= 0.06 Btu/lb-°R
k	= 1×10^{-4} Btu/in-sec-°F
heat production rate	= 0
ambient temperature	= 70°F
capsule initial temperature	= 700°F
h mean	= 3 Btu/ft ² -hr-°F (Reference 9)

~~CONFIDENTIAL~~

~~CONFIDENTIAL~~
RECORDED

Approximate fuel properties can be simulated by using either depleted UO_2 microspheres or a 14 percent W-86 percent Mo microsphere mixture.

Figure III-29 indicates that roughly 8 minutes will elapse before the monitored temperature of the outer shell reaches 500°F under the assumed conditions. Appreciable wind (~ 15 knots) or much lower ambient temperature will reduce the available test time. Obviously, the initial temperature can be changed to compensate for ambient conditions and/or yield a different amount of test time.

3. Conclusions

The major conclusions derived from the aerodynamic and thermal analyses of the spherical fuel capsule are:

- (1) Total heat input to the spherical capsules is a strong function of average capsule density for diameters between one and five inches.
- (2) Peak heating rate for a two inch fuel capsule released at 283,000 feet occurs at about 190,000 feet.
- (3) The impact velocity of an intact two inch fuel capsule is approximately 335 feet/sec.
- (4) Recession rate of Ta-10W alloy above 3800°F is on the order of 0.04 inch/sec under postulated reentry conditions.
- (5) Final two inch capsule configurations will burn and disperse fuel only a few seconds after release if they are subjected to stagnation heating following an orbital decay.
- (6) Stability of the capsule is an important factor but release from orbital decay with a sizable tumble rate will still result in a stable fuel-down attitude by 190,000 feet. The analysis must include both uniform and stagnation heating cases as either can occur.

~~CONFIDENTIAL~~
RECORDED

Figure III-29. Impact Test Temperature Transient Analysis

~~CONFIDENTIAL~~
~~RECORDED~~

- (7) Uniformly heated fuel capsules with a diameter of approximately two inches will have fuel exposed about 20 seconds after release at 283,000 feet.
- (8) Any type of orbital decay or abort and release after more than 186 seconds of a nominal booster trajectory will result in fuel dispersal and/or burnup at an altitude greater than 100,000 feet.
- (9) Partial burnup of the two inch spherical fuel capsule will occur for aborts between 135 and 186 seconds on the typical boost trajectory considered. Other nominal boost trajectories should have a similarly narrow partial burnup zone.
- (10) If the fuel capsule is subjected to an early abort which yields enough aerodynamic heating to raise the capsule surface temperature to 2500°F , the surface temperature of the capsule at sea level impact will be $400\text{-}500^{\circ}\text{F}$.
- (11) Insofar as nuclear safety is concerned, some latitude may exist in the thickness of the inner liner and outer shells. For example, addition of 0.010 inch to each cell would not substantially change the reentry destruction potential of the spheres.

C. Capsule Creep Analysis

Capsule volume increases and wall thickness decreases with increasing time because of the creep phenomenon. The volume increase tends to increase capsule life while wall thickness decrease tends to reduce life. Therefore, a comprehensive evaluation of creep characteristics was conducted for several spherical capsule designs. A modification of the extrapolated Larson-Miller technique was used. Normally, this technique is restricted to application of creep-to-rupture data for lifetime prediction. However, it can be used to obtain capsule creep characteristics as a function of time.

~~CONFIDENTIAL~~
~~RECORDED~~

0315087330
~~CONFIDENTIAL~~

The analysis is based upon behavior of a single shell. The Haynes-25/Ta-10W capsule can be analyzed because only the Ta-10W is considered as a pressure containment shell. For the Haynes-25/Haynes-25 combination, cases were run assuming reliance of the inner shell alone, as CAPSPE assumed, and also considering the effect of the outer impact shell. For the double shell analyses, the design was analytically simplified into a single shell model. The resulting error is small due to the small gap between shells. Initially, the inner liner will contain the pressure level without transferring any forces into the outer layer. However, for a two inch diameter capsule and a gap of 5 mils, the double shells will react as a single shell when the inner liner has achieved approximately 0.5 percent creep. This creep value is only a small fraction of the total creep capability prior to rupture. As a result, separate initial inner layer creep was not considered.

The calculation technique for creep analysis is based upon Equations III-1 through III-17. However, instead of using these to predict time-to-rupture, they are applied to predict time to a specified creep. The analysis is performed by using the digital computer program LMCAP, which was written under this contract. Program flow sheets are presented in Appendix A.

A series of Larson-Miller relationships covering various stages of creep prior to rupture are shown in Figures III-30 and III-31 for Haynes-25 and Ta-10W, respectively. These curves are based upon limited experimental data. Therefore, the analysis should be repeated when additional information becomes available.

Selected wall thicknesses obtained by the program CAPSPE (as previously discussed) were analyzed for time dependent creep. The Ta-10W shell creep rate was investigated with and without creep induced volume changes. The results are shown in Figure III-32. The effect of considering time dependent volume and thickness changes is to extend creep life by about five percent at five percent creep. This indicates that the CAPSPE code results are conservative.

Figure III-33 shows the percentage creep of a Haynes-25/Haynes-25 capsule as a function of time with only the inner liner acting as the creep resistant member. Figure III-34 shows the total wall (double shell) behavior. As expected, there is a substantial decrease in percent creep compared to the single shell case.

0317087330
~~CONFIDENTIAL~~

Figure III-30. Larson-Miller Data for Haynes-25

Figure III-31. Larson-Miller Data for Ta-10W

CONFIDENTIAL

Figure III-32. Percent Creep vs. Time for Haynes-25/Ta-10W Capsule

CONFIDENTIAL

Single Shell Creep

Figure III-33. Percent Creep vs. Time for Haynes-25/Haynes-25 Capsule(Single Shell)

Double Shell Creep

Figure III-34. Percent Creep vs. Time for Haynes-25/Haynes-25 Capsule(Double Shell)

~~CONFIDENTIAL~~

Figure III-35 shows the effect of void fraction on the percent creep of two inch 1500°F Haynes-25/Haynes-25 fuel capsules. Only the inner liner is used for pressure containment. Figure III-36 shows a similar plot for two inch 1800°F Haynes-25/Ta-10W capsules.

D. Capsule Burst Pressures

Burst pressure determinations of the reference high and low temperature fuel capsules have been performed. The study considered both the pressure vessel alone and the complete double layer capsule. The results are shown in Figures III-37 and III-38.* As expected, typical burst pressures are much higher than normal operating helium pressures which are less than 500 psia after five years.

E. Impact Analysis

1. Introduction

The experimental phase of this program is directed toward product verification. It consists of a limited number of impact tests to determine the impact velocity required to rupture a specific capsule. The only data obtained was the velocity of impact and the post-test condition of the sample. At the time of the analysis, no useful information regarding the dynamic stress-strain properties of the material nor capsule deformation versus time during impact was available. Nevertheless, considerable insight has been gained. This improves our present understanding of the phenomenon and provides a better basis for impact analysis of spheres.

The deformation process of an impacting spherical capsule is unknown. Therefore, we have developed two models, a "shear" model and a "tension-compression" model. The shear model includes only shear deformation in describing the impact process. The tension-compression model includes only normal stresses. Shear deformation is prominent for thick-

*Burst test results are discussed in Section V.

~~CONFIDENTIAL~~

Figure III-35. Percent Creep vs. Time for Haynes-25/Haynes-25 at Various Void Fractions

Figure III-36. Percent Creep vs. Time for Haynes-25/Ta-10W at Various Void Fractions

~~CONFIDENTIAL~~

Figure III-37. Pressure Required to Attain Yield and Ultimate Stresses vs. Temperature for Haynes-25/Haynes-25 Capsule

~~CONFIDENTIAL~~

~~CONFIDENTIAL~~

Fuel - Pu-238
Inner Capsule Material - Ta-10W
Outer Capsule Material - Haynes-25
Inner Capsule Thickness - 0.020 inch
Outer Capsule Thickness - 0.034 inch
Diameter - 2.0 inches

Figure III-38. Pressure Required to Attain Yield and Ultimate Stresses vs. Temperature for Haynes-25/Ta-10W Capsule

~~CONFIDENTIAL~~

~~CONFIDENTIAL~~

031508700
~~CONFIDENTIAL~~

walled shells. Thin-walled shells deform by the action of normal stresses. Since our actual shell may not fit neatly into either category, the answer probably lies somewhere in between. Hence, the use of two models which bracket the impact process may provide insight into the transition from the initial spherical shape to the deformed shape after impact. This allows correlation of the impact velocity and capsule deformation. In turn, we can define a design limit by selection of the failure criterion.

2. Cylinders Versus Spheres

Considerably more experience has been obtained with the impact of cylinders, especially end-on cylinder impact, than with spheres. It may be informative to consider some similarities and dissimilarities between the two cases. Figure III-39 shows the general nature of the deformation and fracture experienced by a cylinder impacted end-on at its minimum fracture velocity. Plastic deformation is confined to the end of the capsule. The fracture is a conical shear fracture similar in geometry to the compression fracture in a brittle material. The fracture initiates very close to the point of impact unless the capsule design provides significantly higher strength in that region. Typical fracture velocities are of the order of 300 ft/sec. Since the total axial shortening of the capsule is typically of the order of 0.050 inch, the entire impact process is completed in approximately 30 microseconds.

Figure III-40 illustrates the final deformed outer profile of four impacted capsules with their initial profiles superimposed. As indicated, the impacted region is approximately flat with slight bulges at the periphery of the flat surface. The upper surface of the impacted sphere appears to coincide reasonable well with the initial profile, indicating that little deformation of this upper region has occurred.

The most energetic Haynes-25/Haynes-25 capsule showed a partial failure of the inner liner at 561 ft/sec. A complete failure may occur with the next velocity increment to 610 ft/sec. Capsules are undergoing appreciable ductile deformation during impact, being flattened by as much as 0.64 inch at 561 ft/sec. The duration of the impact process is appreciably longer than for the cylindrical end-on impacts, and is of the order of 200 microseconds. The deformation process consists of the formation and

031508700
~~CONFIDENTIAL~~

~~CONFIDENTIAL~~

RESTRICTED

Figure III-39. Schematic of Deformation of a Cylindrical Capsule Impacting

~~CONFIDENTIAL~~

RESTRICTED

03115047338
~~CONFIDENTIAL~~

Figure III-40. Haynes-25/Haynes-25 Capsules;
Profiles Before & After Impact, Scale 1:1

03712047338
~~CONFIDENTIAL~~

~~CONFIDENTIAL~~

REF ID: A63110

growth of a plane circular area of contact between the sphere and the target. In the test at 561 ft/sec this circle of contact had grown almost as large as the equator of the original sphere. When fracture occurs, it probably will have the form of a conical shear fracture at, or very near to, the periphery of the circle of contact. This leads to the interesting conclusion that the fracture will occur late in the impact process, when the capsule has slowed down and when strain rates are low, rather than early in the impact when strain rates are high and the metal might be expected to behave more brittly.

The deformation pattern in the cylindrical capsule is a consequence of the relative velocities of elastic and plastic strain in the material of construction. Elastic strains are transmitted at the speed of sound which is approximately 16,000 ft/sec in high strength alloys. This is high compared to the impact velocity. Plastic strain occurs as a result of the motion of dislocations; it is a cooperative process involving atoms acting over atomic distances. Appreciable inertia is involved and plastic strains are transmitted at a variable rate which is lower than the elastic strain rate and which is a function of the stress level. When elastic stresses build up rapidly, as they do in end-on impact, high stress levels can be attained. This should lead to high plastic strain rates which permit the plastic strain to closely follow the elastic strain. The plastic deformation is confined to the vicinity of impact where the elastic stresses and strains originate and reach high values most quickly. As the inertia of plastic flow increases, the plastic strains probably will follow the elastic stress less readily, and plastic deformation will be more general throughout the specimen.

Analysis of high strain rate deformation is not well developed. The question of whether rate of propagation of plastic deformation is defined by the prior strain only, or whether it is also dependent upon the prior strain rate, is unresolved. Rajnak and Hauser (Reference 10) performed a series of deformation experiments with pure aluminum at various strain rates and derived an analytical representation for use via digital computer. With the relation between stress and strain established empirically for the specific material and under similar conditions of stress distribution and stress rate, they accurately calculated plastic deformation in a long tube impacted on end. The general deformation pattern was similar to that observed in end-on impact. The authors

~~CONFIDENTIAL~~

REF ID: A63110

0311507000
~~CONFIDENTIAL~~

did not carry their experiments to fracture of the sample. It is more difficult to calculate fracture than the deformation pattern because the controlling fracture criterion is not known. However, the methodology of Rajnak and Hauser could in principle be extended to the point of fracture. This would result in the ability to predict deformation and fracture of any size capsule once the behavior of the specific material had been established for the pertinent stress distribution. (The general geometry of the impact must be unchanged.)

We must obtain a deformation model to equate kinetic energy to the work of plastic deformation. Plastic deformation is a highly irreversible process. The energy consumed between any two end points is therefore a strong function of the route followed. Consequently, analysis of spherical capsule impact requires the mode of deformation prevailing during impact.

Figure III-41 has been prepared from a photograph (Reference 11) of a hemispherical-cylindrical sample impacted at Sandia and from our reconstruction of what the capsule looked like before impact. This sample was made of 304 stainless steel by machining from bar stock and was filled with unconsolidated molybdenum powder to simulate the fuel. Its wall thickness was stated to be 0.100 inch. The wall thickness to radius ratio is about 0.158, and the outside diameter is approximately 1.25 inch. This capsule is appreciably smaller and thicker than the capsules prepared on the present program. The sample failed with a conical fracture surface near the periphery of the contact area at a velocity of 605 ft/sec. Study of this behavior will assist in spherical capsule impact analysis.

The spherical capsule impact process obviously begins with the sphere touching the plane target at a single point of tangency. As the impact proceeds, the point of tangency changes to a circular plane. The capsule velocity will drop as its kinetic energy is expended in plastic deformation. A small fraction of the kinetic energy will be stored as elastic strain in the capsule. This will result in rebound at impact termination.

Direct evidence is not available concerning the exact mechanism by which deformation proceeds. Examination of the final shapes of a series of capsules impacted at increasing velocities is not necessarily representative of the sequence of shapes which a high velocity capsule passes through. The

0311507000
~~CONFIDENTIAL~~

~~CONFIDENTIAL~~

~~UNCLASSIFIED~~

Figure III-41. Impact Deformation of Thick Walled Hemispherical Cylindrical Sample, Scale 4:1

~~CONFIDENTIAL~~

~~UNCLASSIFIED~~

031501000
~~CONFIDENTIAL~~

strain rates are not equivalent at corresponding stages of deformation. The final shape assumed by a capsule impacted at half of fracture velocity is probably determined by the slow deformation rate that prevails when the capsule has expended most of its kinetic energy. Probably the transient shape of a high velocity capsule will be more angular, with less deformation in advance of the contact plane than the final shape assumed by a slow capsule.

3. Shear Model

a. General. Consider the marked thickening of the flattened portion of the capsule shown in Figure III-41. Except for the region close to the center of the impact area, the thickness of the flattened section is equal to the distance through the undeformed wall projected in the direction of impact (in Figure III-41, $ab = cd$). Now postulate that the process of deformation is one of continuous shear of the wall at the line of intersection of the spherical surface with the target plane. This is shear due to compressive loading and occurs on a conical surface oriented approximately 50° from the plane of contact and shown in Figure III-40 as the cone of fracture. It is further postulated that during the high velocity impact little bulging of the spherical wall occurs in advance of the shear cone. Since the fracture process absorbs little energy, it is unlikely that the kinetic energy will be completely exhausted at the instant of fracture. The bulging of the sphere above the fracture probably occurred as a result of residual kinetic energy after fracturing. It is difficult to define the specific cause of the fracture. Fracture probably results near the end of the impact process due to the combined effects of increasing shear angle and decreasing fracture strength associated with reduced strain rates as the kinetic energy nears exhaustion.

In this model, the mass of fuel is considered to exert negligible influence upon capsule wall failure. Due to its unconsolidated nature, the fuel can exert only compressive loads upon the capsule. These loads will be directed primarily to the flattened portion of the capsule where they will be without effect upon the capsule deformation. Most of the kinetic energy of the fuel mass will be expended in fragmentation and heating of the fuel mass itself. A portion may cause bulging of the spherical capsule wall.

031501000
~~CONFIDENTIAL~~

~~CONFIDENTIAL~~

The deformation mechanism is less clear in the spherical capsules impacted in the present program. This impact test program is not complete, and full fracture has not been obtained. The capsules are thinner walled than the sample in Figure III-40. In addition, the capsules are double walled. Nevertheless, the basic mechanism of deformation may be the same. Stress calculations based upon this model are presented in the next section.

b. Stress Analysis. Figure III-42 illustrates a spherical capsule during impact. According to the postulated model, the high velocity portion of the impact, during which most of the kinetic energy is expended, proceeds by a shear deformation. This is localized near the intersection of the spherical wall and the target plane. The shear region grows from a point, at the point of original contact, to a ring which expands in diameter during the impact. The energy desorbption rate rises rapidly during impact since both the volume being sheared and the angle of shear increase. As a result, capsule deceleration is non-linear, probably rising to a maximum late in the impact process.

The incremental volume in which shearing occurs is:

$$dv = 2\pi r_p R d\theta, \text{ or:} \quad (\text{III-23})$$

$$dv = 2\pi R^2 \sin \theta d\theta \quad (\text{III-24})$$

The incremental work of deformation is:

$$dw = dv \tau \tan \gamma \quad (\text{III-25})$$

where:

$$\begin{aligned} \tau &= \text{dynamic shear stress} \\ \tan \gamma &= \text{shear strain} \\ &= \tan \theta \end{aligned}$$

The work of deformation is:

$$w = 2\pi R^2 \int_0^\theta \tau \tan \theta' \sin \theta' d\theta' \quad (\text{III-26})$$

~~CONFIDENTIAL~~

031507978
~~CONFIDENTIAL~~

Figure III-42. Geometry of Impacting Spherical Capsule

0371278
~~CONFIDENTIAL~~

~~CONFIDENTIAL~~
DECLASSIFIED

At present, the relationship between τ and θ can only be established empirically. To proceed further, we must make assumptions to obtain approximate dynamic shear stress-strain relationships. Static tensile data on Haynes-25 alloy at 600°F are repeated as:

yield stress	43,700 psi
ultimate stress	127,500 psi
strain at fracture	71 percent

These data will be converted to the desired data by means of:

$$\sigma_d = \frac{4}{3} \sigma_s \quad (\text{Reference 12}) \quad (\text{III-27})$$

also,

$$\sigma_d = 2\tau_d \quad (\text{III-28})$$

and,

$$\tan \gamma = \sqrt{2\epsilon^2 + 4\epsilon + 1} - 1 \quad (\text{Reference 13}) \quad (\text{III-29})$$

Rearranging yields,

$$\tau_d = 0.77 \sigma_s \quad (\text{III-30})$$

$$\tan \gamma = 1.74 \epsilon \quad (\text{III-31})$$

where:

- σ = stress
- ϵ = strain
- s refers to static
- d refers to dynamic

These relationships are not rigorous but they permit further analysis. For better accuracy, the relationships for τ and γ must be established experimentally at strain rates comparable to those in the actual impact. It is further necessary to assume a rate of strain hardening to extrapolate the stress-strain relationship to high strains. The shear strains observed in the impact, when converted to tensile strain by the relationship above, are of the order of 1.5. This is reasonable since the stress pattern is triaxial. It will be assumed that elastic strains are negligible and that the rate of strain hardening is constant. (The material is of the rigid-linear work hardening type.) Applying these assumptions yields the stress-strain relationships shown in Figure III-43.

~~CONFIDENTIAL~~
DECLASSIFIED

~~CONFIDENTIAL~~

The Haynes-25/Haynes-25 capsules in the present program have a 2.00 inch outer diameter and two walls of 0.034 inch each. The wall will be treated as a single wall of 0.068 inch. The capsule has a wall thickness to radius ratio of 0.068, compared to 0.158 for the sample in Figure III-41. Table III-4 shows the weights and test velocities of these capsules.

TABLE III-4. CAPSULE WEIGHTS AND TEST VELOCITIES

Capsule Number	PR-3	PR-4	PR-5	PR-6
Capsule Weight (g)	279.59	283.00	284.77	280.95
Fuel Weight (g)	147.49	148.29	154.00	154.00
Velocity (ft/sec)	429.00	452.00	528.00	561.00

The last capsule, fired at 561 ft/sec, showed a partial fracture on the inner wall and probably represents a close approach to fracture velocity. Additional capsules are undergoing aging at Sandia. These will be tested at higher velocities.

Figure III-40 shows the outer profile of each capsule after impact and, superimposed, the initial profile. These permit determination of θ for each test from:

$$(R-h) = R \cos \theta \quad (\text{III-32})$$

Based on these values of θ , and the materials properties of Figure III-43, a graphical integration to determine the deformation work was carried out. After substitution of the capsule dimensions, the expression for work becomes:

$$w = 0.44 \int_0^{\theta_f} \tau \tan \theta \sin \theta \, d\theta \quad (\text{III-33})$$

where θ_f is θ at the end of impact. This work is compared to the kinetic energy of the capsule prior to impact in Table III-5.

~~CONFIDENTIAL~~

Figure III-43. Stress-Strain Relationships for Haynes-25 at 600°F
(Reference Union Carbide, Haynes Alloy No. 25, June 1962)

TABLE III-5. KINETIC ENERGY COMPARISON PRIOR TO IMPACT

Capsule	PR-3	PR-4	PR-5	PR-6
Kinetic Energy, Capsule only (ft-lbs)	1740	1980	2720	3030
Kinetic Energy, Total mass (ft-lbs)	2660	3020	4200	4680
(R-h) (inch)	0.46	0.44	0.39	0.36
θ	60°	65°10'	67°	68°50'
Plastic Work (ft-lbs)	4330	6200	7170	8390

The plastic work calculated on the basis of the proposed model yields results which are too high by a factor of 2.5 to 3.1 if we assume the kinetic energy of the fuel does not contribute to capsule fracture. If the total kinetic energy including the fuel is considered, the calculated plastic work is high by a factor of 1.7 to 2.1.

The assumptions made in establishing a relationship between dynamic shear stress and strain are not rigorous and contribute significant error to the solution. An error as large as 50 percent is unlikely and, therefore, an exact stress-strain relationship would not resolve the discrepancy. The assumption that the spherical wall does not bulge in advance of the impact front probably is over-simplified. If appreciable bulging occurs, γ may be appreciably less than θ , and significantly less energy would be absorbed in the deformation process.

A more complete solution for the impact process will require two experimental programs. The first would determine actual stress-strain relationships through the point of fracture. The second would determine the actual deformation mode during impact. These data would permit further refinement in the "shear model" solution and should make possible the calculation of the failure velocity for the material tested. To extend the analysis, it would be necessary to determine the stress-strain relationships for each new material.

4. Tension - Compression Model

a. General. This model assumes that the impact deformation proceeds through action of normal stresses in the shell wall. As in the shear model, impact deformation is determined by energy considerations. The internal

~~CONFIDENTIAL~~

strain energy is equated to the kinetic energy of impact. However, the internal strain energy is derived from normal stresses in the capsule wall whereas in the shear model, strain energy was assumed to be derived from shear stresses. The internal strain energy due to capsule impact is assumed to be equal to the energy necessary to change the capsule from its initial spherical shape to the final shape after impact. The final shape is assumed to take the form shown in Figure III-44. The impacted surface is flat, with an approximately cylindrical surface connecting the flat surface with the upper, approximately spherical surface.

For purposes of partitioning the strain energy, the overall deformation may be described as tension and compression of the impact surface and tension of the upper, roughly spherical surface. As such, the total strain energy may be divided into a tension component and a compression component. The sum must be equal to the total impact strain energy.

b. Tensile Model. The tensile model assumes the bottom portion of the sphere is flattened which causes the small circle, at a distance X above the impact point, to enlarge as shown in Figure III-45. The expansion of the shell at the enlarged small circle is $[2\pi\beta - 2\pi A]$. Further:

$$A^2 = R^2 - (R-X)^2 = R^2 - R^2 + 2RX - X^2$$
$$A = (2RX - X^2)^{1/2} \quad (\text{III-34})$$

$$\sin(\theta) = \frac{A}{R} \quad (\text{III-35})$$

$$(\theta) = \sin^{-1} \left(\frac{A}{R} \right) \quad (\text{III-36})$$

$$\beta = R(\theta) = R \sin^{-1} \left(\frac{A}{R} \right) = R \sin^{-1} \left[\frac{\sqrt{2RX - X^2}}{R} \right] \quad (\text{III-37})$$

C = original circumference of small circle

$$C = 2\pi A$$

~~CONFIDENTIAL~~

031591000

~~CONFIDENTIAL~~

Figure III-44 Assumed Impacted Shape

0312081000

~~CONFIDENTIAL~~

~~CONFIDENTIAL~~

Idealized Strain Distribution

Enlarged Small Circle

Figure III-45. Tensile Model

~~CONFIDENTIAL~~

0315087037
CONFIDENTIAL

$$\Delta C = 2 \pi \beta - 2 \pi A \quad (III-38)$$

$$\epsilon_M = \frac{\Delta C}{C} = \frac{2 \pi \beta - 2 \pi A}{2 \pi A} = \frac{\beta}{A} - 1 \quad (III-39)$$

$$\epsilon_M = \frac{R \sin^{-1} \frac{\sqrt{2RX - X^2}}{R}}{\sqrt{2RX - X^2}} - 1 \quad (III-40)$$

ϵ_M = Tensile model circumferential strain

This is the maximum tensile strain in the system. The distribution is indicated in idealized form as the shaded portion of Figure III-45. Strain along a polar great circle is assumed negligible.

c. Compression Model. The compression model assumes the upper portion of the shell to be a rigid surface. By compressing the lower spherical cap section of the sphere into the surface area bounded by the small circle limiting the impacted surface, the surface of the cap will be in compression along polar great circles. This is illustrated in Figure III-46. The compressive strain in the flattened cap in the radial direction is:

$$\epsilon_R = \frac{\beta - A}{\beta} = 1 - \frac{A}{\beta} \quad (III-41)$$

where, as in the tensile model:

$$A = (2RX' - X'^2)^{1/2} \quad (III-42)$$

and:

$$\beta = R \sin^{-1} \frac{(2RX' - X'^2)^{1/2}}{R} \quad (III-42)$$

so that:

$$\epsilon_R = 1 - \frac{(2RX' - X'^2)^{1/2}}{R \sin^{-1} \frac{[2RX' - X'^2]^{1/2}}{R}} \quad (III-44)$$

0372087037
CONFIDENTIAL

~~CONFIDENTIAL~~

RESTRICTED

Figure III-46. Compression Model

~~CONFIDENTIAL~~

RESTRICTED

0315587030
~~CONFIDENTIAL~~

Meridinal tensile strain in this impacted surface is assumed to be accounted for in the tensile model. Calculations indicate that this is a reasonable assumption.

d. Complete Tension Compression Model. At actual impact the measured deflection will be called X. The maximum strain energy that can be absorbed in the tension model will be at this X deflection. The maximum strain energy that can be absorbed in the compression model will also be at this common X. Therefore, if this accounts for all the plastic strain in the sphere, the maximum energy the sphere can absorb in deflecting to the point X is the sum of the energy of the compression model and the tension model, or:

$$E_{\text{total}} = E_{\text{tension (max)}} + E_{\text{compression (max)}} \quad (\text{III-45})$$

Letting $X = X'$ in Equation (III-44) yields

$$\beta_{\text{tension}} = \beta_{\text{compression}} \quad (\text{III-46})$$

$$A_{\text{tension}} = A_{\text{compression}} \quad (\text{III-47})$$

Using:

$$\epsilon_R = 1 - \frac{A}{\beta} \quad (\text{III-48})$$

and, from Equation (III-39)

$$\epsilon_M = \frac{\beta}{A} - 1 \quad (\text{III-49})$$

the tensile strain is related to the compression strain by:

$$\epsilon_R = \frac{\epsilon_M}{1 + \epsilon_M} \quad (\text{III-50})$$

The maximum energy absorbed in the tension model is assumed to be:

$$E_T = \left[(\text{Volume})_{\text{tension}} \right] \int_0^{\epsilon_M} \sigma_T \cdot d\epsilon \quad (\text{III-51})$$

0317200000
~~CONFIDENTIAL~~

~~CONFIDENTIAL~~
REF ID: A66318

where:

$$(\text{Volume})_{\text{tension}} = 4\pi R^2 t \quad (\text{III-52})$$

Since the material is assumed to be rigid-linear strain hardening, the integral is given by:

$$E_T = 4\pi R^2 t \epsilon_M \left(Y_T + \frac{1}{2} k_T \epsilon_M \right) \quad (\text{III-53})$$

in which Y_T is the tensile yield strength and k_T is the slope of the tensile plastic stress-strain curve. The term, $4\pi R^2 t \epsilon_M$ describes a lunar wedge of plastic strain volume equivalent to the strain volume defined in Figure III-45.

The maximum strain energy absorbed in the compression model is assumed to be:

$$E_C = (\text{Volume})_{\text{compression}} \int_0^{\epsilon_R} \sigma_c \cdot d\epsilon \quad (\text{III-54})$$

where:

$$(\text{Volume})_{\text{compression}} = 2\pi R X t \quad (\text{III-55})$$

The integral is given by:

$$E_C = \left[2\pi R t \epsilon_R \left(Y_C + \frac{1}{2} k_C \epsilon_C \right) X \right] \quad (\text{III-56})$$

where $2\pi R t \epsilon_R$ defines a compressed ring equivalent to the strain area of Figure III-46, Y_C is the compressive yield strength of the capsule wall material and k_C is the slope of the compressive stress-strain curve.

The total strain energy is found by substituting Equations (III-53) and (III-56) into (III-45).

$$E_{\text{total}} = \left[4\pi R^2 t \epsilon_M \left(Y_T + \frac{1}{2} k_T \epsilon_M \right) + 2\pi R t \epsilon_R \left(Y_C + \frac{1}{2} k_C \epsilon_R \right) X \right] \quad (\text{III-57})$$

~~CONFIDENTIAL~~
REF ID: A66318

~~CONFIDENTIAL~~

Substitution of Equation (III-50) into (III-57) yields:

$$E_{\text{total}} = 4\pi R^2 t \epsilon_M \left(Y_T + \frac{1}{2} k_T \epsilon_M \right) + 2\pi R t \left(\frac{\epsilon_M}{1 + \epsilon_M} \right) \left[Y_c + \frac{1}{2} k_c \left(\frac{\epsilon_M}{1 + \epsilon_M} \right) \right] X \quad (\text{III-58})$$

where ϵ_M is given by Equation (III-40).

By equating the total strain energy to the kinetic energy of impact of the system, there results:

$$\frac{mV^2}{2} = 2\pi R t \epsilon_M \left[2R \left(Y_T + \frac{1}{2} k_T \epsilon_M \right) + \frac{X}{1 + \epsilon_M} \left(Y_c + \frac{1}{2} \cdot \frac{k_c \epsilon_M}{1 + \epsilon_M} \right) \right] \quad (\text{III-59})$$

where m is the capsule mass and V is impact velocity. Equation (III-59) represents the single-walled thin spherical shell under the imposed impact criteria. It relates capsule deformation and impact velocity.

e. Concentric Shells. Concentric shells of different materials present problems due to the allowable strains and response rates of the materials prior to rupture. Therefore, the model is more suitable to single-walled shells or concentric shells of the same material. However, with care, in conjunction with the stress-strain relationship of the materials under consideration, reasonable accuracy can be obtained by extending Equation (III-59) to include concentric shells. The deflection of each shell is identical if the radial gap between shells is negligible. Equation (III-59) can be modified to yield:

$$\frac{mV^2}{2} = 2\pi R \epsilon_M \left[2R t_1 \left(Y_{T1} + \frac{1}{2} k_{T1} \epsilon_M \right) + \frac{X}{1 + \epsilon_M} \left(Y_{c1} + \frac{1}{2} \cdot \frac{k_{c1} \epsilon_M}{1 + \epsilon_M} \right) \right] + 2\pi R \epsilon_M \left[2R t_2 \left(Y_{T2} + \frac{1}{2} k_{T2} \epsilon_M \right) + \frac{X}{1 + \epsilon_M} \left(Y_{c2} + \frac{1}{2} \cdot \frac{k_{c2} \epsilon_M}{1 + \epsilon_M} \right) \right]$$

~~CONFIDENTIAL~~

140

~~CONFIDENTIAL~~
~~RESTRICTED~~

where the subscripts 1 and 2 refer to the different shell thicknesses and material properties.

f. Design Limit. We placed a limit on the capsule design to establish capsule wall thickness prior to testing. This was necessary to insure capsule survival by selecting a conservative situation. The limit cannot be directly developed from the described impact models. The model limit is given by ultimate stress-strain values. The capsule limit was established through the coincidence of two separate factors predicting a point or zone of limiting X (model vertical deflection).

g. Shear Limit. Taylor (Reference 13), in his membrane model, predicts the point of maximum shear to occur at $X = 0.5R$. Goldsmith (Reference 14), in a solid spherical model, predicts the point of maximum difference in the principle stress (point of maximum shear in Mohr's circle) to occur at $X = 0.48R$. Since the maximum ultimate shear stress values of the materials used in the capsule are not known, a reasonable model limit would be to limit the deflection at the point of maximum shear.

h. Departure from Model Geometry. Figures III-40 and III-45 illustrate that there exists a point in the deformation at which the flat impacted lower surface of the shell will form an approximate right angle with the upper roughly spherical surface. At this point the wall between the equatorial weld and the flattened bottom becomes straight and forms a cylindrical section. At this point, the wall may buckle, fold over, and form a radical departure from the geometry of the impact models.

In addition, at this point large shear stresses would occur if the sphere were a thick wall vessel. Since it is analyzed as a thin wall in this tension-compression model, this type of shear stress cannot be predicted, however, the departure of the real sphere from a membrane model would determine the amount of shear.

A third possibility occurs due to this 90° discontinuity. It may present a region for the reflection of plastic and elastic waves; and it has been found that, in cylindrical impact, the reflection and interaction of these waves determined failure criteria. Therefore, it is possible that strain energy models may not apply beyond the discontinuity.

~~CONFIDENTIAL~~
~~RESTRICTED~~

CONFIDENTIAL

The earliest point at which this 90° angle can occur in the analysis is when B equals R in the tension model. When B equals R, θ is one radian. Solving for the X we find:

$$\theta = 1 \text{ rad}$$

$$R \cos \theta = h = (R - X)$$

$$R(0.54) = R - X$$

$$X = R (1 - 0.54)$$

$$X = 0.46 R \quad (\text{III-61})$$

Comparison of these factors indicates that the zone of 0.46R to 0.5R deflection may be critical. For the Haynes-25/Haynes-25 capsule, the ductility is sufficiently high to enable the deflection X to go considerably beyond this zone. Therefore, for preliminary design the 0.46R to 0.5R deflection limit was selected as conservative, and used as the design criterion. For the Haynes-25/Ta-10W capsule, the Ta-10W ultimate strain value closely coincides with this zone, and in this sphere the design limit is less conservative.

5. Correlation of Analysis and Preliminary Test Results

The preliminary test results and analytical predictions are presented in Figure III-47. The test data are between the two models. The data should curve toward the origin and follow the tension-compression model at lower velocities. The tension-compression model predictions diverge from the test results for velocities above approximately 350 ft/sec and deformation of approximately 0.5R. A possible explanation has been described in Section 4, above. The 0.46R to 0.5R deformation range is considered critical for two reasons. At this point, the deformed shape has departed from the assumed shape. In addition, maximum shear occurs in this deformation range and contributes significant energy to the deformation process.

The shear model predictions are approximately parallel to the test results. These predictions are uniformly unconservative over the velocity range considered. The behavior indicates that shear corrections to

CONFIDENTIAL

Figure III-47. Experiment and Analysis Comparison

CONFIDENTIAL

0315587030
~~CONFIDENTIAL~~

the tension-compression model are necessary for deformations greater than 0.48R. This may bring it into closer alignment with the high velocity test results.

6. Recommendations

The tension-compression model should be corrected for shear deformation when the capsule begins to depart from the assumed deformed shape. This would entail corrections for the bulge around the periphery of the flat impacted surface. However, if the interior fuel retaining plate is removed or weakened, this bulge may not appear, or it may be so small as to be negligible. The effect of this fuel retaining plate may be resolved by further tests on capsules either without the plate or with a much weakened plate.

The effect of fuel deformation and its interaction with the capsule wall should be determined. More complete dynamic stress-strain data and equations for the capsule wall material are necessary. In addition, ultimate stress-strain characteristics at the impact test strain ratio are required.

F. Performance Test Capsule Design

As discussed in Section II.C, two types of spherical capsules were designed for performance testing. In the test capsules, a fuel simulant was used. The capsules were pressurized to simulate helium release from the fuel after a nominal one year shelf life. The design temperatures anticipated during impact were based on a high altitude, suborbital, random reentry. As a result, the capsules were significantly below operation temperatures.

1. Design Criteria

Mechanical design of the test capsules is based on the data presented in Tables III-1 and III-6. Two minor changes from the reported optimum design were made for simplicity and economy. The use of one wall dimension for the Haynes-25 hemispheres of the Haynes-25/Haynes-25 and Haynes-25/Ta-10W capsule systems allowed procurement of a single stock thickness. In addition, designing both capsule systems to the same capsule and liner diameter reduced the required number of hemisphere fabrication tools. Similarly, these changes reduced the number of capsule fabrication processes required.

0317030
~~CONFIDENTIAL~~

~~CONFIDENTIAL~~

DECLASSIFIED

TABLE III-6. MECHANICAL DESIGN CRITERION

	<u>Index Capsules</u>			
	<u>Inner Liner</u>	<u>Outer Shell</u>	<u>Inner Liner</u>	<u>Outer Shell</u>
1. Material	Haynes-25	Haynes-25	Ta-10W	Haynes-25
2. Wall Thickness (in)	0.034	0.034	0.020	0.034
3. Inner Diameter (in)	1.8575 $\pm$ 0.001	1.935 $\pm$ 0.001	1.8855 $\pm$ 0.001	1.9375 $\pm$ 0.001
4. Outer Diameter (in)	1.9255 $\pm$ 0.004	2.0055 $\pm$ 0.004	1.9255 $\pm$ 0.004	2.0055 $\pm$ 0.004
5. Radial Clearance Between Shells (in)	0.0035 <u>0.0085</u>		0.0035 <u>0.0085</u>	
6. Fuel Simulant	W-Mo	---	W-Mo	---
7. Fill Gas	He	He	He	He
8. Internal Pressure (Required to Pro- duce 140 psi at Operating Temp.)	19.4 psig	0 psig	18.1 psig	0 psig
9. Total Weight of Capsule (empty)	0.126 lbs	0.187 lbs	0.138 lbs	0.187 lbs
10. Total Weight of Capsule Assemblies Filled with Fuel Simulant	0.674 lbs*		0.695 lbs*	
11. Assumed Void Fraction of Capsule	0.75	---	0.75	---
12. Fuel Compartment (Volume Fraction)	0.45	---	0.45	---
13. Void Fraction Vol- ume in Fuel Compartment	0.20 (typ)	---	0.20 (typ)	---

*Calculated nominal capsule weight excluding backup and seal plugs.

~~CONFIDENTIAL~~

DECLASSIFIED

0315087000
~~CONFIDENTIAL~~

2. Basic Mechanical Design

The major components of the test capsule are shown in Figure III-48. Each capsule consists of:

- (a) An inner pressure containment liner,
- (b) An outer impact resistant shell,
- (c) A ring shaped weld insert at the equator of each inner liner,
- (d) A fuel retainer plate inside the bottom inner liner,
- (e) Fuel simulant contained under the plate.

The capsule was designed considering present hot cell fuel loading and handling and the requirements for high quality and reliability in fabrication and testing.

The inner liner was designed to allow most of the component fabrication, joining, testing, and inspection to be performed prior to fueling. This includes assembly and joining to the fuel retainer plates, weld backup rings and inner shell hemispheres. Further, it allows complete non-destructive testing and inspection of the major circumferential weld joint before fueling.

Fueling is accomplished by pouring fuel through the 0.125 inch hole in the bottom hemisphere. The fuel fill hole is then sealed by welding in a plug.

A similar hole, 0.062 inch in diameter, was provided in the top inner hemisphere opposite the fuel cavity. This allowed evacuation and helium backfilling after the fuel fill port seal had been made. Small diameter holes were placed in the center of the fuel retainer plate to allow gas passage and aid in evacuation and helium backfill. Plug insertion and final seal welding was performed after the proper helium atmosphere was obtained. The inner liner could then be cleaned to minimize contamination,* nested within the two outer impact hemispheres and then joined by welding. A nominal annulus was required between the spheres to eliminate melting between the two spheres or possible incomplete penetration on the circumferential weld on the outer sphere. To maintain this gap, a spacer was welded to the inside diameter of the outer hemisphere prior to assembly. As with the inner liner, an atmosphere evacuation and helium backfill port was built into the top of the outer shell.

* in a fueled capsule

84
~~CONFIDENTIAL~~
0315087000

~~CONFIDENTIAL~~

Figure III-48. General Configuration of the Spherical Capsule

~~CONFIDENTIAL~~

0310507031
~~CONFIDENTIAL~~

3. Component Details

a. Outer Hemisphere. The outer hemisphere diameters of the Haynes-25/Haynes-25, and Haynes-25/Ta-10W spheres were selected to allow interchangeability with either of the inner spheres. They were designed for maximum strength under impact. The reference weld joint is a butt configuration of the dimensions, ovality, and flatness shown in Figure III-49. The hemisphere diameter was held to a ± 0.001 inch tolerance to assure proper alignment, interchangeability and clearance. The spacer wire was 0.005 to 0.007 inch thick with a rectangular cross section.

b. Inner Hemispheres. The Haynes-25 and Ta-10W inner hemispheres have the same outside diameter, but vary on their inside diameter. Other characteristics are similar to the outer shell hemispheres.

c. Weld Backup Ring. The weld backup ring has a "T" cross section. The bottom edge has the same diameter as the hemisphere outside diameter. The "T" configuration serves as a weld backup ring and provides a ledge for maintaining the fuel retainer plate position. The ring was made of the inner liner material.

d. Fuel Retainer Plate. The fuel retainer plate is flat, 0.015 inch thick, and is also made of the inner liner material. Tolerance between the inside diameter of the inner capsule and the outside diameter of the retainer plate is held between a 0.001 inch clearance and an interference fit. The fuel retainer plate is designed to withstand the shock and vibration loads of missile launch, yet fail under impact conditions. Failure at impact avoids the concentration of reaction loads between the inner shell and the retainer plate.

The plate provides a barrier between the fuel and its void volume. Therefore, it must provide a helium path. Five 0.0015 inch diameter holes accomplish this. They are small enough to stop fuel, but large enough to allow gas release.

4. Tolerance Study

A tolerance study of the Ta-10W inner liner and Haynes-25/Haynes-25 complete capsule was made. The established tolerances are shown in Figure III-50.

0310507031
~~CONFIDENTIAL~~

- NOTES.
- 6 THIS TOLERANCE ADDED TO REFERENCE DIMENSION TO AID IN FINAL INSPECTION
 - 5 KEEP INDIVIDUAL DIMENSIONAL INSPECTION SHEET FOR EACH PART DURING FABRICATION TO BE FURNISHED WITH SHIPPED PART
 - 4 NO MARKING (OF ANY FORM) TO APPEAR ON PARTS
 - 3 MIN OF .002 SURFACE SCRATCH DEPTH
 - 2 ALL MACHINED SURFACES TO HAVE $\sqrt{32}$ RMS FINISH
 - 1 INTERPRET DRAWING IN ACCORDANCE WITH STANDARDS PRESCRIBED BY MIL STD. 8-C

Figure III-49. Spherical Capsule Component Details

a. Haynes-25 / 5/H

b. Ta-10W Inner Liner

Figure III-50. Spherical Capsule Tolerance Study

5. Fuel and Pressure Simulation

a. Fuel Simulant and Capsule Volume. A thermal load of 60 watts requires 154 grams (0.339 lbs) of fuel.* Table III-7 shows that PuO_2 microspheres pack to 6.40 gms/cc. The fuel loading requires 24.1 cc. The fuel occupies 43.7 percent of the Haynes-25 liner and 41.8 percent of the Ta-10W liner volumes.

The PuO_2 fuel was simulated by using molybdenum and tungsten powders adjusted to match the weight and volume of microspheres.

b. Internal Liner Pressure. Helium closely follows the perfect gas law. Hence, inner liner pressure is directly proportional to temperature. At 1800°F , the Haynes-25/Ta-10W capsule will contain 140 psia. Correcting this for the void fraction in the test capsule gives 18.1 psig for the Haynes-25/Ta-10W and 19.4 psig for the Haynes-25/Haynes-25 capsules at room temperature.

TABLE III-7. LINER VOLUME**

	<u>Ta-10W Liner</u>		<u>Haynes-25 Liner</u>	
Total Volume in Liner Sphere	57.6	cc	55.1	cc
Volume of Fuel Retainer Plate	0.68	cc	0.68	cc
Volume of Void Plus Fuel	56.9	cc	54.4	cc
Volume of Packed Fuel Microsphere	24.1	cc	24.1	cc
Volume of PuO_2 at 60 Percent	14.5	cc	14.5	cc
Packing Fraction	0.64	cc	0.64	cc
Volume of Total Void	42.4	cc	39.9	cc
Void Fraction of Capsule Liner	0.745	cc	0.734	cc
Density of Packed Fuel Microspheres	6.40	g/cc	6.40	g/cc

**Monthly Progress Letter No. 12 - SNAP-19 Radioisotope Power Supply, MND-3607-110, September 15, 1966 (CRD). Data are for 88 to 150 micron microspheres.

*0.39 watts/gm

0315047030

~~CONFIDENTIAL~~

IV. CAPSULE DEVELOPMENT AND FABRICATION

A. Materials Procurement

All component materials were ordered from commercial suppliers in standard mill forms (sheet, rod, wire, and tube). To control quality, all stock was ordered to recognized Society of Automotive Engineers "AMS" specifications. Haynes-25 was ordered against AMS-5537B or AMS-5759C. Tantalum-10 tungsten stock was ordered against AMS-7847 and AMS-7848. A certified analysis was obtained for each material. These data are reported in Tables IV-1 and IV-2. The metal powder used for fuel simulant was certified to meet the data given in Table IV-3. It was obtained as -80 +250 mesh (0.0022 to 0.0070 inch).

B. Capsule Components Procurement

Capsule component procurement was split into development type components to study the joining and assembly parameters and production components for the test capsules.

1. Development Components

Seventy-six Haynes-25 hemispheres were ordered to develop welding parameters, assembly techniques, evacuation and atmosphere filling procedures, and closure processes. These included 36 inner liner hemispheres and 36 outer shell hemispheres. Twelve Ta-10W inner liner hemispheres were also fabricated.

Hemispheres were fabricated by simple hydroforming from flat sheet stock. The weld rings and fuel retainer plates were machined from flat stock to yield the required fits with the formed inner hemispheres. Considerable variation existed in the dimensional tolerances. Hemisphere wall thickness variation was about 0.010 inch and radius variations ranged to 0.020 inch. Similar variations occurred in weld rings and retainer plates. These were permitted in the development components only to meet scheduling requirements.

0315047030
~~CONFIDENTIAL~~

TABLE IV-1. HAYNES-25 (L-605) STOCK

Certified Property Data

Component	Heat No.	C	Chemical Analysis in w/o					W	Ni	Co	Fe
			Mn	Si	S	P	Cr				
Hemispheres	B-18648	0.072	1.60	0.33	0.009	0.004	19.92	14.47	10.32	Bal.	1.73
Rings	B-18465	0.088	1.55	0.36	0.011	0.008	19.80	15.06	10.19	Bal.	2.52
Retainer Plates	B-18354	0.085	1.72	0.33	0.011	0.007	19.64	14.91	10.14	Bal.	2.05
Rod-Hole Plugs											
0.250" Dia.	186-5-1201	0.15	1.24	0.40	0.010	0.016	19.60	14.70	10.73	Bal.	2.65
0.125" Dia.	5362	0.111	1.69	0.15	0.010	0.003	20.20	14.70	10.05	Bal.	0.45
0.0625" Dia.	5362	0.111	1.69	0.15	0.010	0.003	20.20	14.70	10.05	Bal.	0.45
Wire-Shim											
0.020" Dia.	186-4-1702	0.12	1.43	0.15	0.012	0.014	19.63	14.78	10.42	Bal.	2.11
Tubing											
125 O. D. x0.030 wall	B-10175	0.12	1.20	0.33	0.004	0.012	19.92	15.58	9.88	50.80	1.94

Room Temperature Mechanical PropertiesStress Rupture

Heat No.	Yield-psi (0.2% Offset)	Tensile-psi	Elongation (% in 2")	Stress psi	Temp. (°F)	Hours	Elongation - %
B-18648	66,800	138,100	54.0	24,000	1500	51.6	22.6
B-18465	65,100	136,200	64.0	24,000	1500	89.4	17.7
B-18354	63,600	134,100	38.5	24,000	1500	64.6	48.2
186-5-1201	---	141,000	---	---	---	---	---
5362	---	149,000	---	---	---	---	---
5362	---	148,000	---	---	---	---	---
186-4-1702	---	145,000	---	---	---	---	---
B-10175	---	152,700	52.0	---	---	---	---

CONFIDENTIAL

CONFIDENTIAL

TABLE IV-2. TANTALUM-10 TUNGSTEN STOCKCertified Property DataChemical Analysis in PPM

Component	Heat No.	O	N	C	Al	Cr	Cu	Fe	Mo	Nb	Ni	Ti	W*	Ta
Hemispheres														
0.060" thick	3240	32	25	18	<25	<5	<1	10	10	<25	<5	< 5	10.1%	Bal.
Ring														
0.025" thick	3323	43	24	33	<10	<5	<5	<10	50	200	<5	< 5	9.0%	Bal.
Retainer Plates														
0.015" thick	5128	21	20	44	<25	<5	<5	10	<10	100	15	< 5	9.6%	Bal.
Rod-Hole Plugs														
0.250" Dia.	5128	21	20	44	<25	<5	5	10	<10	100	15	< 5	9.6%	Bal.
0.125" Dia.	3493	21	22	26	<25	<5	3	5	25	---	<5	<10	10.7%	Bal.
0.0625" Dia.	3493	21	22	26	<25	<5	3	5	25	---	<5	<10	10.7%	Bal.
Tube	3170	38	25	23	<15	<5	<1	15	<10	<25	<5	< 5	9.6%	Bal.

*All Tungsten Values In Weight Percent

Room Temperature Mechanical Properties

Heat No.	Yield (psi-0.2% Offset)	Tensile (psi)	Elongation (% in 2")
3240	---	---	---
3323	76,100	89,900	22%
5128	71,700	94,800	26%
5128	---	---	---
3493	---	---	---
3493	---	---	---
3170	---	---	---

~~CONFIDENTIAL~~

DECLASSIFIED

TABLE IV-3. MOLYBDENUM AND TUNGSTEN POWDERS
CERTIFIED PROPERTY DATA

Powder	Chemical Analysis in w/o*							
	P	Al	C	S	Co	O	Fe	Mn
Molybdenum	0.001	0.001	0.020	0.001	0.001	0.01	0.05	0.001
Tungsten	0.001	0.001	0.020	0.001	0.001	0.01	0.05	0.001

Powder	Chemical Analysis in w/o*							
	N	Ni	Pb	Sn	Mo	W	H	Si
Molybdenum	0.003	0.10	0.001	0.001	99.5 (min)	---	0.005	0.05
Tungsten	0.003	0.10	0.001	0.001	---	99.5 (min)	0.005	0.05

*All values maximum w/o certified except for molybdenum and tungsten

~~CONFIDENTIAL~~

DECLASSIFIED

0315587030

~~CONFIDENTIAL~~

2. Production Components

Forty sets of capsule components were procured to the requirements of Figure III-45. These consisted of 20 sets of Ta-10W inner liner sphere components, 20 sets of Haynes-25 inner liner sphere components, and 40 sets of Haynes-25 outer sphere components. One set of components for a Haynes-25/Haynes-25 system is shown in Figure IV-1.

Close dimensional control was required on the individual hemispheres. This necessitated a three phase fabrication process consisting of a four step cold forming operation, a multipass spinning phase, and contour machining to final size. Three intermediate anneals were required to fabricate the Haynes-25 parts and one anneal was required with the Ta-10W. These were required to remove work hardening. The weld rings and retainer plates were precision machined. Fabrication of hemispheres, rings, and retainer plates required precision dies for the forming and machining operations. All parts were supplied in the fully annealed condition.

Some out-of-specification Ta-10W hemisphere wall thicknesses were used due to variation in sheet stock thickness. Fabrication of replacement components was not feasible because of long delivery schedules. The out-of-specification Ta-10W used for impact and creep was within 0.0005 to 0.0010 inch of specifications.

The plugs used to seal the fuel and atmosphere fill holes were fabricated from Haynes-25 and Ta-10W rod stock of the correct diameter. They were precision machined to the proper length.

Holes in the fuel retainer plates were made by the Elox electrical discharge technique. The center section of the 0.015 inch thick retainer plate was first counterbored 0.007/0.008 inch. (The counterbore area was rectangular in shape, about 3/8 by 1/16 inch.) The five 0.0015 ± 0.0004 inch diameter holes were Eloxed through the remaining stock thickness.

031703~~CONFIDENTIAL~~

Figure IV-1. Fabricated Spherical Capsule Components

~~CONFIDENTIAL~~

-95-

~~CONFIDENTIAL~~

~~CONFIDENTIAL~~

~~CONFIDENTIAL~~

03115087030

~~CONFIDENTIAL~~

C. Tooling Design and Fabrication

A flat plate welding jig and a circumferential welding chamber were designed and fabricated. Both were designed for a TIG (Tungsten-Inert-Gas) welding process. Four testing and inspection tools were built.

1. Flat Plate Welding Jig

A flat plate welding jig was designed and built to establish preliminary welding parameters. It is shown in Figure IV-2. The jig consists of a specimen holding block, a drive mechanism, torch holder, and instrumentation. An HW-25 Model Linde Torch is held in the positioning fixture which is fitted with micrometer adjustments for horizontal and vertical travel. This fixture rides on a carriage supported by zero clearance linear bearings traveling on two precision ground shafts. The carriage assembly is driven by a variable speed electric motor through a positive drive rack and pinion gear train. The unit can travel at speeds to 36 inches per minute.

2. Circumferential Welding Jig

A circumferential welding jig was designed and fabricated to weld the spherical capsule components under simulated hot cell conditions, prevent oxide contamination of the joints and parent metal, and insure high purity inert gas filling of test capsules. The unit is shown in Figure IV-3. It consists of a cylindrical closed chamber modified for view ports, gas inlets, vacuum, and instrumentation connections. The base plate supports the specimen chill block holder; circular drive mechanism; torch positioner; and vacuum, welder, and instrumentation connections. Use of various chill blocks, specimen holders, and torch positions allows different welding operations for various spherical capsule joints (plate to ring, atmosphere and fuel fill plug; and circumferential hemisphere joints).

3. Miscellaneous Tooling

Four dimensional inspection and mechanical property tools were designed and fabricated. These include a bend test tool for flat plate weld specimens, a machining template for tensile testing of weld joints, and two dimensional measuring jigs for hemisphere diameter and wall thickness.

03115087030
~~CONFIDENTIAL~~

Figure IV-2. Flat Plate Welding Jig

~~CONFIDENTIAL~~
REF ID: A60316

-97-

~~CONFIDENTIAL~~
REF ID: A60316

031538700

~~CONFIDENTIAL~~

Figure IV-3. Spherical Welding Jig

037000000 ~~CONFIDENTIAL~~

~~CONFIDENTIAL~~

DECLASSIFIED

D. Welding and Assembly Development

1. Flat Plate Welding Studies

Welding studies were initiated on flat plate Haynes-25 and Ta-10W to obtain:

- (a) A simple and economical method of establishing preliminary welding parameters (current, speed, arc gap, electrode size, and cover gas requirements);
- (b) A simple geometry to prepare bend and tensile test specimens for evaluation of weld joints and heat affect areas;
- (c) Quick initiation of development welding without waiting for final design test capsule components.

Two welded flat plate specimens are shown in Figure IV-4.

a. Haynes-25 Alloy. Eight parameters were evaluated in the Haynes-25 flat plate, welding studies.

- (1) Stock thickness,
- (2) Joint configuration,
- (3) Current,
- (4) Speed,
- (5) Arc gap,
- (6) Electrode size,
- (7) Cover gas,
- (8) Cover gas flow rate.

About 150 welds were made on the flat plate jig TIG welding techniques and triplicate specimens. The stock thicknesses and joint configurations were selected based on the design requirements for both the inner liner and outer shell circumferential joints.

The first study established the basic welding parameters for 0.038 inch thick sheet in a straight butt joint configuration. Six of the welding parameters were varied to establish the best welding conditions:

~~CONFIDENTIAL~~

DECLASSIFIED

0315087030

~~CONFIDENTIAL~~

- (1) Electrode Size - 0.020, 0.040, and 0.062 inch diameter in straight tungsten and two percent thoriated tungsten;
- (2) Cover Gas - Commercial argon, ultra-high-purity argon, and a 50:50 mixture of argon and helium;
- (3) Cover Gas Flow rate - 5 to 45 CFH;
- (4) Welding Speed - 4 to 25 inches per minute;
- (5) Arc Gap - 0.005 to 0.050 inch;
- (6) Current - 35 to 65 amps.

The welded specimens were evaluated by visual, dimensional, dye penetrant, and metallographic inspection. When the best set of parameters was selected, a verification rerun was performed on five specimens. The results showed that metallurgically sound welds could be prepared which were free of cracks and pores. The optimum set of parameters for 0.038 inch thick Haynes-25 sheet stock was found to be:

- (1) Electrode Size - 0.040 inch diameter tungsten - 2 w/o percent thorium;
- (2) Cover Gas - Ultra-high-purity argon at 30 CFH;
- (3) Arc Gap - 0.030 inch (arc voltage - 10.0 - 11.0);
- (4) Speed - 16 3/4 inches per minute;
- (5) Current - 49 amps DCSP.

The second parametric study on flat plate welds evaluated the effects of 0.030 inch and 0.033 inch sheet stock thickness. Electrode size and type, and cover gas flow rate type were fixed at the optimum parameters selected above. The arc gap, speed, and current were then varied in a range about half that described for the 0.038 inch stock. Results showed that sound welds could be made with both the 0.030 and 0.033 inch thick stock using the same welding parameters except for the current. The optimum currents for the 0.030 and 0.033 inch thick stock were 45 and 47 amps, respectively.

031702080000
~~CONFIDENTIAL~~

Haynes-25

Ta-10W

Figure IV-4. Flat Plate Weld Specimens

~~CONFIDENTIAL~~
-101-
50703160

~~CONFIDENTIAL~~
50703160

0310587030

~~CONFIDENTIAL~~

The third flat plate welding study evaluated joint configurations. Three types of joints were selected:

- (1) Straight butt,
- (2) Simple lap,
- (3) Tapered butt (See Figure IV-5).

The plate edges of all three Haynes-25 stock thicknesses were first machined. Then the plates were welded using the reference parameters listed above while varying welding current. Good welds were made with all joint configurations in all thicknesses.

In addition to visual, dimensional, dye penetrant, and metallography testing and inspection, specimens of each type of weld were evaluated by room temperature bend and tensile strength testing. Bend tests were performed according to ASTM-E-190-61T on duplicate samples of all welds. Tensile tests were made on triplicate specimens for each type of weld. For comparison purposes, both bend and tensile tests were also run on the as-received sheet stock and on welds which had been given a solution heat treatment at 2200°F in argon for one hour.

The thoriated tungsten electrode was less brittle after the initial welds. The 0.020 inch diameter electrode was too thin, often melting during use. The 0.040 inch diameter yielded a narrow weld and heat affect zone. A blunt tipped electrode gave the narrowest weld bead.

Cover gas studies showed that ultra-high-purity-argon resulted in less contamination on the surface and within the fusion zone of the weld. Commercial argon gave satisfactory results except for oxidation. Helium-argon mixture offered no advantage in penetration, but made arc starting, arc stability, and cleanliness more difficult to attain.

Arc gaps around 0.030 inch appeared optimum, although little difference was found within 0.010 inch of the value. Smaller arc gaps often caused electrode tungsten contamination, and blow-holes. Larger arc gaps improved penetrations but exhibited less arc stability and wider variations in weld penetration and width.

0310587030
~~CONFIDENTIAL~~

~~CONFIDENTIAL~~

RESTRICTED

Butt Geometry

Lap Geometry

10° Taper - Butt Geometry

"X" - Stock Thickness

Figure IV-5. Cross Sectional Configurations of Flat Plate Weld Joints

~~CONFIDENTIAL~~

RESTRICTED

~~CONFIDENTIAL~~

Welding current and speed were important variables. This material hot cracks easily in heat affect zones. High power inputs are used to get the heat quickly into the joint, and proper chilling is used to quickly remove the heat. One-quarter by one inch cross section chills were used. However, burn-through of the stock occurs even at fast welding speeds, if too high a current is used.

Welding parameters were adjusted during initial evaluation to obtain a weld joint with the narrowest possible fusion and heat affect zones, but with full penetration. Dimensional inspection showed only 0.001 to 0.005 inch buildup of fused metal on the weld surface. Dye penetration inspection showed that welds free of surface cracks, pores, and pits could be attained if proper attention is given to surface preparation, cleanliness, and cover gas flow rates. Heat affect zone cracking occurred when the sample was allowed to overheat during the welding. Metallographic evaluation of the flat plate specimens showed that joints free of internal voids, cracks, inclusions, or other detrimental effects could be obtained at the reference welding conditions. Typical views of six of these welds are shown in Figure IV-6.

The Haynes-25 sheet thicknesses had little effect on other welding variables. Small current increases were required with increasing stock thickness. The three thicknesses of stock were obtained from five different heats of Haynes-25 alloy. Variance of material composition produced no significant changes.

Bend test studies of the flat plate welds showed good weld and heat affect zone ductility at room temperature. All weld specimens survived a 4T^{*} bend when ground edges were used to prevent formation of stress-risers due to cutting or shearing deformations. Both transverse and longitudinal directions of the weld were tested, as well as face and root bends. Specimens with the 10° taper joint and the straight butt joint could survive the 1T bend without fracture. Edge cracking was encountered in the lap joint specimens at bends 3 to 2T.

*A bend of four times the material thickness.

~~CONFIDENTIAL~~

~~CONFIDENTIAL~~

Test results are summarized in Table IV-4. Values are reported for the wrought stock, as-welded, and welded and heat treated specimens. All tensile tests were made across the weld joint. Note that the 10° tapered joint is the strongest joint in all three material thicknesses. The lap joint is the weakest. Heat treatment of the welded structure appears to improve the strength by two to seven percent. All of the tensile specimens of the heat treated and most of the as-welded butt and 10° tapered joints broke outside of the weld and heat affected zone. Approximately one-third of lap joint weld specimens failed in the weld or heat affected zone when tested either in the as-welded or heat treated condition.

b. Tantalum-10 Tungsten Stock. A similar study was made on flat plate Ta-10W stock. Two thicknesses were investigated using only the butt joint configuration. Approximately 30 welds were made using the same jig and setup reported for the Haynes alloy. A typical Ta-10W specimen is shown in Figure IV-4.

A parametric evaluation of electrode size, arc gap, welding speed, and current was performed. Only ultra-high-purity argon was used to prevent oxide contamination. Visual, dimensional, dye penetrant, and metallographic evaluation showed that good welds could be prepared with this alloy at the following parameters:

- (1) Electrode - 1/16 inch diameter blunt tip (W-2% Th),
- (2) Arc Gap - 0.040 inch,
- (3) Speed - 16 3/4 inches per minute,
- (4) Current- 55 amps for 0.015 inch and 60 amps for 0.020 inch sheet (DCSP).

A few welds were made at 90 amps at 30 inches per minute. This increased the fusion zone width.

Metallographic examination showed good weld structure with a minimum of grain growth. Some porosity was found, probably due to gas entrapped during welding, oxide and water vapor. Figure IV-7 shows typical photomicrographs of these welds. Visual and dimensional inspection showed that welds similar to the Haynes-25 stock could be achieved. Dye penetrant inspection gave no indications of surface defects, cracks or flaws.

~~CONFIDENTIAL~~

Transverse View 45X Magnification

0.038 Inch Stock

Butt
Joints

0.033 Inch Stock

Lap
Joints

10° Taper
Joints

Figure IV-6. Photomicrographs Haynes-25 Plate Welds

Transverse View

50X Magnification

0.020 Inch Stock - Butt Joint

Figure IV-7. Photomicrographs Tantalum - 10 w/o Tungsten

TABLE IV-4. TENSILE TEST DATA FOR FLAT PLATE HAYNES-25 STOCK

<u>Thickness and Joint Condition</u>	<u>As-Received</u>	<u>Tensile Strengths in Psi</u>	
		<u>As-Welded</u>	<u>As-Welded and Heat Treated</u>
0.030	133,100	---	---
Butt Joint	---	120,100	123,900
Lap Joint	---	119,900	129,200
10° Taper Butt	---	127,000	134,300
0.033	133,000	---	---
Butt Joint	---	121,900	125,000
Lap Joint	---	120,800	124,200
10° Taper Butt	---	124,700	135,300
0.038	143,300	---	---
Butt Joint	--	132,500	136,400
Lap Joint	---	120,800	125,000
10° Taper Butt	---	142,400	145,100

Heat Treatment - Annealed at 2200°F in argon for one hour and quenched.

CONFIDENTIAL

-107-

CONFIDENTIAL

03105047030

~~CONFIDENTIAL~~

Room temperature bend tests were made in the same manner as reported for Haynes-25. All welds were deformed to a 4T bend. Ta-10W welds which exhibited small weld grain size, as observed on specimen surfaces, could survive a 2T bend without fracture. The larger grain size specimens failed at about 3T bends.

Room temperature weld tensile strengths were measured. Due to oxidation problems, no heat treated specimens were tested. The tensile strength of the wrought starting stock was 89,400 psi and the butt welded specimens had a tensile strength of 89,800. Both values reported are for 0.020 inch thick Ta-10W stock averaged from four specimens per sample. The tensile ductility of the welded specimens was approximately 90 percent of that measured for the wrought stock.

2. Flat Ring Welding Studies

Translating the flat plate welding parameters to a spherical geometry using rings of flat plate stock was studied. Approximately 18 units were prepared of both Haynes-25 and Ta-10W. The specimens were two inches in diameter and one half inch high. These were studied by:

- (a) Forming flat strips complete with butt or lap joint configurations;
- (b) Positioning within shaped chill blocks,
- (c) Evaluating the preheat, weld, and decay cycles of current and time based on the welding parameters established in the flat plate study.

Two specimens are shown in Figure IV-8.

Butt and lap joint configurations were evaluated with 0.030, 0.033, and 0.038 inch thick Haynes-25 sheet. Following welding, the specimens were evaluated by visual, dimensional, dye penetrant, and metallographic techniques. The results showed that good welds could be made at the following parameters:

- (a) Electrode Size and Shape - 0.040 inch diameter
W-2% Th-blunt tip,
- (b) Cover Gas - ultra-high-purity-argon at 15 CFH,

03105047030

~~CONFIDENTIAL~~

~~CONFIDENTIAL~~

REF ID: A62110

Haynes-25

Ta-10W

Figure IV-8. Flat Plate Ring Weld Specimens

~~CONFIDENTIAL~~

REF ID: A62110

031558703

~~CONFIDENTIAL~~

- (c) Arc Gap - 0.040 inch,
- (d) Speed - 16 3/4 inches per minute,
- (e) Preheat Time - 2 seconds,
- (f) Weld Cycle - 1 1/2 revolutions
- (g) Decay Time - 18 seconds,
- (h) Welding Current - 74 amps.

3. Component Welding and Assembly Studies

The preliminary fabrication sequence established for spherical capsules is shown schematically in Figure IV-9. The development effort is detailed below.

a. Haynes-25 Liner Spheres

(1) Fuel Plate to Weld Ring Subassembly. Standard resistance spot welding techniques were first used to attach the plate to the weld ring. Good welds were obtained at pressures of 15 psi and a current of 125 amps. However, buckling of the non-welded area left spaces where fuel simulant powder could pass and the weld joints were weak. Spot welds were abandoned.

Approximately ten TIG welds were made using different chill blocks, electrode sizes and tip configurations, and holding methods. These were made in the spherical welding jig. The method of chilling to prevent melting of the entire ring and peel back of the edge of the retainer plate at the joint were the main problems encountered. The chilling arrangement developed is shown in Figure IV-10 (View A). Excellent plate to ring welds were made at the following conditions:

- (a) Electrode - 0.040 inch diameter, W-2% Th tapered tip,
- (b) Arc Gap - 0.025 inch,
- (c) Speed - 16 3/4 inches per minute,
- (d) Current - 22 amps,
- (e) Weld Cycle - 1 1/3 revolutions.

Visual, dimensional, and metallographic inspection of these joints showed good, tight, crack free welds with no melting at the main body or tab of the weld ring. Good dimensional control was obtained with no plate or ring distortion.

031558703

~~CONFIDENTIAL~~

Figure IV-9. Capsule Fabrication Sequence

0315587030

~~CONFIDENTIAL~~

Figure 10a. Plate to Ring Weld Chill

Figure 10b. Liner Circumferential Weld Chills

Figure 10c. Backup, Helium, and Fuel Plug Weld Chills

Figure IV-10. Welding Chill Configurations (Cross Sectional Views)

0315587030
~~CONFIDENTIAL~~

DECLASSIFIED
~~CONFIDENTIAL~~

(2) Assembly of the Inner Sphere. Special spherical chills were designed and fabricated for the inner sphere weld joint. These are shown in Figures IV-3 and IV-10 (View B). Assembly of individual parts proved to be simple. While the development parts did not meet the close tolerances required for test components, the plate-ring sub-assembly was easily placed within the liner hemispheres. Then the assembled sphere was fitted into the bottom chill of the welding jig, aligned, and the top chill fitted over the assembly.

About ten sets of liner hemispheres and plate-to-ring subassemblies were used. Only the arc gap and current were varied. Good welds were made with the following parameters:

- (a) Electrode - 0.040 inch diameter, W-2% Th, blunt tip,
- (b) Arc Gap - 0.030 inch,
- (c) Speed - 16 3/4 inches per minute,
- (d) Current - 76 amps,
- (e) Weld Cycle - 1 1/3 revolutions.

All welds were inspected by visual, dye penetrant, and metallographic techniques. High quality, full penetration welds were obtained, which were free of cracks, pores, or other detrimental defects. The completed spheres were also helium leak tested to a sensitivity of better than 10^{-10} cm³/sec (std.). No leaks were found. Minimum distortion occurred during welding and weld buildup on the face of the joint was less than 0.003 inch.

(3) Fuel Filling of the Inner Sphere. Fuel simulant filling was based on methods applicable to "hot cell" loading of an actual radioisotope fuel. The simulant powders were loaded using a special fill funnel and were packed using ultrasonic and mechanical vibration. No problems were encountered.

(4) Helium Filling the Inner Sphere. A pressurized helium fill was required to simulate helium gas resulting from radioisotope decay. This was obtained by placing the fueled liner within the weld chamber in position for the final fill plug weld. The plug used to fill the hole was fitted into a push rod attachment and the chamber was evacuated to

CONFIDENTIAL

0315507031

~~CONFIDENTIAL~~

5×10^{-4} torr. Helium was introduced into the chamber to 19.4 psig. After ten minutes at pressure the fill plug was inserted and the filled sphere was ready for seal welding.

(5) Sealing the Fuel and Helium Fill Holes. The helium pressurization and sealing of the fuel and atmosphere fill holes were significant developments. The seal requirements were similar to the circumferential weld joints. The welds had to be full penetration with sufficient strength and ductility to contain internal pressure and survive impact tests.

Three fill hold designs were evaluated, as shown in Figure IV-11. We first investigated a simple plug geometry (Type A). Both 0.125 and 0.250 inch diameter plugs were studied. Holes were drilled in the hemispheres and reamed to size. Plugs, the thickness of the hemisphere wall, were then tapped into place and TIG welded at both atmospheric pressure and with 5 to 20 psig inside the hemisphere. The results were poor. Wall thinning occurred in the weld area. An internal pressure blew weld metal out of the joint.

We next tried Type B (Figure IV-11). We felt that increasing the hemisphere wall thickness near the weld joint would solve the thinning problem and allow full thickness welds. The Type B button plugs were machined with a 3/8 inch diameter at the base and a 1/4 inch land diameter. Length of the land was equal to the wall thickness. The inside plug face was machined to match the diametrical curvature. The object was to first weld the button plug to the inside of the hemisphere as shown in Figure IV-11. Then a hole could be drilled in the welded area and reamed to accept the fuel or atmosphere fill plugs.

Weld attempts without chills were unsuccessful. The hemisphere wall melted and left holes and voids. Therefore, several chills were studied and the one shown schematically in Figure IV-10 (View C) was selected.

Fit of the plug to the inside diameter of the hemisphere was found to be a limiting factor. Poor fits resulted in discontinuous weld joints.

0315507031

~~CONFIDENTIAL~~

~~CONFIDENTIAL~~

Type "A"
Simple Plug

Type "B"
Button Plug

Type "C"
Backup Plug

Figure IV-11. Fill Hole Configuration* (For Fuel and Helium)

* Cross Section Views Through Plug Area

0313507074

~~CONFIDENTIAL~~

These results led us to a simple 1/4 inch backup plug which was less expensive. We first drilled and reamed the hemispheres to accept a 0.250 inch plug (0.080 inch long) of the Type C geometry shown in Figure IV-11. This plug was welded to the hemisphere from the back side as shown. The welded area was drilled and reamed to accept a 0.125 inch fuel fill plug or a 0.062 inch helium fill plug. The appropriate plug was tapped in and the seal weld made to the backup plug from the outside surface of the hemisphere. The chill configuration shown in Figure IV-10 (View C) was used for both plug welds.

About ten welds of both the fuel and helium fill joints were made using this approach. With some, only hemispheres were used with either atmospheric or a 20 psig pressure on the inside of the hemisphere. With the others, the backup plugs were first welded into the hemispheres and the weld areas drilled and reamed for the plugs. Then these hemispheres were welded into full spheres and the seal plugs inserted and welded to close the sphere.

The optimum welding parameters for the backup plug welds were.

- (a) Plug Size - 0.250 inch diameter by 0.080 inch long,
- (b) Electrode - 0.040 inch diameter, W-2% Th - tapered tip,
- (c) Arc Gap - 0.030 inch,
- (d) Speed - 16 3/4 inches per minute,
- (e) Current - 18 amps,
- (f) Weld Cycle - 2 revolutions.

The optimum welding parameters for the fuel and helium fill plugs were:

- (a) Plug Size - 0.125 inch diameter by 0.080 inch long (fuel),
0.062 inch diameter by 0.125 inch long (helium),
- (b) Electrode Size - 0.040 inch diameter, W-2% Th-tapered tip,
- (c) Arc Gap - 0.030 inch,
- (d) Speed - 16 3/4 inches per minute,
- (e) Current - 20 amps,
- (f) Weld Cycle - 1 1/3 revolutions.

0313507074

~~CONFIDENTIAL~~

~~CONFIDENTIAL~~

DECLASSIFIED

All specimens were evaluated by visual, dimensional, dye penetrant, helium leak, and metallographic techniques. The process yielded sound welds, free of cracks, pores, leaks, etc., and weld penetrations were equal to or greater than the hemisphere wall thickness.

b. Tantalum-10 Tungsten Liner Spheres. The Ta-10W liner was similar to the Haynes-25 liner except in thickness of the sphere wall, inside liner diameter, and dimensions of the weld ring and retainer plates. Development of the same five joining-assembly steps was required. The processes developed were identical except for certain welding parameters and the requirement for better atmosphere protection during welding. Six sets of liner sphere components were procured and used for parametric study of weld joint variables.

The optimum parameters for the fuel plate to ring weld were:

- (1) Electrode - 0.040 inch diameter, W-2% Th-tapered tip,
- (2) Arc Gap - 0.025 inch,
- (3) Speed - 16 3/4 inches per minute,
- (4) Current - 52 amps,
- (5) Weld Cycle - 1 1/3 revolutions.

Optimum parameters for the liner circumferential weld were:

- (1) Electrode - 1/16 inch diameter, W-2% Th-blunt tip,
- (2) Arc Gap - 0.030 inch,
- (3) Speed - 16 3/4 inches per minute,
- (4) Current - 100 amps,
- (5) Weld Cycle - 1 1/3 revolutions.

Backup plug optimum parameters were:

- (1) Plug Size - 0.250 inch diameter by 0.080 inch long,
- (2) Electrode - 0.040 inch diameter, W-2% Th-tapered tip
- (3) Arc Gap - 0.030 inch,
- (4) Speed - 58 inches per minute,
- (5) Current - 56 amps,
- (6) Weld Cycle - 2 revolutions.

~~CONFIDENTIAL~~

DECLASSIFIED

0315087130

~~CONFIDENTIAL~~

The best fuel and helium fill plug welds were obtained with:

- (1) Plug Size - 0.125 inch diameter by 0.080 inch long (fuel),
0.062 inch diameter by 0.125 inch long (helium),
- (2) Electrode - 0.040 inch diameter, W-2% Th-tapered tip,
- (3) Arc Gap - 0.030 inch,
- (4) Speed - 58 inches per minute,
- (5) Current - 62 amps,
- (6) Weld Cycle - 1 1/3 revolutions.

Gas filling and mechanical assembly processes used with the refractory liner fabrication were identical to those used for the super-alloy except three evacuations to 5×10^{-6} torr followed by ultra-high-purity argon purge were used. Oxidation was found near the weld joint and traced to metal powder outgassing. All subsequent refractory liners were filled with molybdenum and tungsten powders which had been vacuum outgassed.

All welds were evaluated by visual, dimensional, dye penetrant, helium leak, and metallographic techniques. High quality welds were achieved which were equal to or better than those obtained in the flat plate and ring welding of this alloy. In addition, the pores found in the fusion zones of the plate and ring welds were not observed in the capsule welds. We think this is due to the high vacuum and high purity gas processing.

c. Capsule Assembly and Outer Shell Fabrication

(1) Fabrication and Joining of Wire Spacers. A wire spacer was required to position the inner liner within the outer impact sphere and to assure a minimum space between the inner sphere and the circumferential outer hemisphere joint during welding. This was between 0.003 and 0.008 inch thick. The cross sectional area was small and flat to minimize effects on impact testing.

Spacers were made of 0.020 inch diameter, Haynes-25 wire stock which was rolled to a rectangular cross section. Six to twelve inch lengths were cold rolled in eight to ten passes. These were cut to 5 1/2 inch lengths and positioned on the hemisphere inside surface about 0.5 inch below the circumferential edge. This allowed about 0.5 inch space between the wire ends for gas flow during evacuation and helium filling. The wire was resistance spot welded to the outer shell.

0315087130
~~CONFIDENTIAL~~

~~CONFIDENTIAL~~
REF ID: A66378

(2) Capsule Assembly and Circumferential Welding. After the spacer wires were attached, the liner sphere was placed within the outer hemispheres and the circumferential joint sealed by welding. To assure a snug fit, each liner and outer hemisphere was measured, the nominal clearance calculated, and the spacer wires rolled to the exact radial clearance. To keep the outer hemispheres in contact at the circumferential joint, four TIG spot welds were used at 90° spacings around the circumference.

Outer hemisphere welding was similar to that used for the liner circumferential joint. The parameters studied were those resulting from the flat plate and ring studies. About ten circumferential welds were made. A problem resulted due to blow holes and discontinuous welds caused by gas pressure buildup between the liner sphere and the outer shell. This occurred at the end of the weld cycle when the capsule was sealed and helium gas was trapped between the parts. It was corrected by adding a hole in the center of the upper shell hemisphere. This acted as a gas escape hole to relieve pressure during circumferential welding and provided for helium filling.

Good circumferential welds were made at the following parameters:

- (a) Electrode - 0.040 inch diameter, W-2% Th-blunt tip,
- (b) Arc Gap - 0.030 inch,
- (c) Speed - 16 3/4 inches per minute,
- (d) Current - 54 amps,
- (e) Weld Cycle - 1 1/3 revolutions.

All welds were visually, dimensionally, dye penetrant, and metallographically inspected. In addition, the welded sphere was helium leak checked. Welds were metallurgically sound and free of cracks, voids, and helium leaks. Full wall thickness penetrations were obtained, and no melting of the liner sphere or fusion between the liner and impact spheres was encountered.

~~CONFIDENTIAL~~
REF ID: A66378

03115587030

~~CONFIDENTIAL~~

(3) Filling the Capsule with Helium. Next, the space between the liner and impact spheres was filled with helium gas. The welding jig was used as previously described, except that only one atmosphere of gas pressure was used.

(4) Sealing the Helium Fill Hole. The final capsule fabrication step was welding the helium fill plug to the top of the outer impact shell. This was accomplished in the same manner as used for the fuel and helium fill plugs for the inner Haynes-25 liner. However, no backup plug was required due to lower helium pressure. Good welds were made in the welding chamber at the following parameters:

- (a) Electrode - 0.040 inch diameter, W-2% Th-tapered tip,
- (b) Arc Gap - 0.030 inch,
- (c) Speed - 16 3/4 inches per minute,
- (d) Current - 18 amps,
- (e) Weld Cycle - 2 revolutions.

This weld was inspected by helium leak checks of the sealed capsule and visual, dimensional, dye penetrant, and metallographic inspection of the joints. No detrimental defects were found.

4. Process Verification Studies

Five Haynes-25/Haynes-25 capsule assemblies were fabricated using the optimum welding processes. Incoming parts, subassemblies, finished spheres, and assembled capsules were inspected by visual, dimensional, dye penetrant, and helium leak tests (where applicable). Two of the five units were destructively inspected using dimensional and metallographic methods. All units were completely satisfactory. Figure IV-12 shows one destructively tested capsule prior to complete sectioning.

Three of these units were sent to Sandia Corporation for initial studies of testing methods and equipment checkout for the impact tests. These units survived the 500°F impacts at velocities above 360 feet per second.

~~CONFIDENTIAL~~

~~CONFIDENTIAL~~

Figure IV-12. Development Phase Spherical Capsule
Haynes-25/Haynes-25 System

~~CONFIDENTIAL~~

CONFIDENTIAL

E. Fabrication of Performance Test Capsules

At least twenty-two performance test capsules were to be manufactured. This included:

- (1) 18 impact capsules (10 Haynes-25/Haynes-25 units and 8 Haynes-25/Ta-10W),
- (2) 2 burst test specimens (1 Haynes-25 and 1 Ta-10W),
- (3) 2 creep test specimens (1 Haynes-25 and 1 Ta-10W).

Quality was assured by:

- (1) All parts and components were inspected visually for defects and cleanliness, and dimensionally for size;
- (2) A qualification run was made on both capsule systems prior to initiating manufacture of deliverable components. All qualification operations were run under the same standardized and controlled processes used for production;
- (3) Checks were made on the process and product during manufacture by:
 - (a) All assembled and/or welded components and parts were non-destructively inspected following each operation. This included visual dimensional, dye penetrant, and leak testing where applicable;
 - (b) In each fabrication run, at least one of the units was destructively sectioned, the welds evaluated by metallographic examination, and appropriate dimensional analysis made of affected parts;
- (4) The finished capsule assemblies were given a complete inspection and evaluation by visual, dye penetrant, and dimensional methods.

CONFIDENTIAL

~~CONFIDENTIAL~~

1. Impact Test Capsules

a. Haynes-25/Haynes-25 Capsules. Two capsules were fabricated and destructively evaluated prior to initiation of manufacture. Photomicrographs of weld joints are shown in Figure IV-13. Both units completely satisfied design requirements. In actual manufacturing, fourteen capsules were fabricated in two runs. Eleven capsules described in Table IV-5, were delivered to Sandia Corporation for impact testing. The others were destructively tested for in-process-control.

b. Haynes-25/Ta-10W Capsules. Two qualification capsules were prepared prior to initiation of manufacture. Both units were destructively tested and evaluated, and completely satisfied design requirements. Two manufacturing runs were made to produce ten Haynes-25/Ta-10W capsules. Eight were delivered to Sandia Corporation, as shown in Table IV-5, and the other two were destructively tested.

2. Burst and Creep Test Specimens

These were special components consisting of only the inner liner sphere with a tubular attachment, as shown in Figure IV-14. Fabrication differed from normal liner manufacture only in:

- (a) Preparing the backup plug welds. Only one hemisphere contained a welded and drilled backup plug. As no fuel simulant was used in these capsules, no fuel fill joint was used;
- (b) Welding of two types of tubular extensions to the helium plug area of the top hemisphere. A six inch length of Haynes-25 or Ta-10W tubing was used for the burst test capsules and the creep test specimens used a 24 inch length.

Two Haynes-25 and two Ta-10W units were fabricated as qualification specimens. All four were completely tested and inspected in the normal manner.

a. Burst Test Units. Two Haynes-25 liners and one Ta-10W liner were fabricated. No in-process-control specimens were used but both were given a complete non-destructive evaluation after fabrication and were found acceptable.

~~CONFIDENTIAL~~

~~CLASSIFIED~~

031530730

~~CONFIDENTIAL~~

Liner Circumferential

Shell Circumferential

Fill Plug

Figure IV-13. Photomicrographs of Qualification Capsule Weld Joints
Haynes-25/Haynes-25 System

031728130

~~CONFIDENTIAL~~

TABLE IV-5. DATA ON DELIVERED IMPACT TEST CAPSULES

<u>Capsule No.*</u>	<u>Capsule Wt.(g)</u>	<u>Fuel Wt. (g)</u>	<u>Capsule Diameter (in)</u>	<u>Capsule Material</u>
PR-3	279.59	147.49	2.010 - 1.998	Haynes-25/Haynes-25
PR-4	283.00	148.29	2.004 - 1.994	Haynes-25/Haynes-25
PR-5	284.77	154.00	2.011 - 1.986	Haynes-25/Haynes-25
PR-6	280.95	154.00	2.008 - 1.987	Haynes-25/Haynes-25
PR-8	286.15	154.00	2.008 - 1.992	Haynes-25/Haynes-25
PR-9	286.55	154.00	2.006 - 1.997	Haynes-25/Haynes-25
PR-10	285.46	154.00	2.003 - 1.997	Haynes-25/Haynes-25
PR-11	285.83	154.00	2.001 - 1.991	Haynes-25/Haynes-25
PR-12	286.86	154.00	2.001 - 1.991	Haynes-25/Haynes-25
PR-14	280.00	154.00	2.003 - 1.996	Haynes-25/Haynes-25
PR-16	284.82	154.00	2.008 - 1.997	Haynes-25/Haynes-25
PR-106	293.04	154.00	2.006 - 1.993	Haynes-25/Ta-10W
PR-108	267.15	133.00	1.996 - 1.989	Haynes-25/Ta-10W
PR-109	295.31	154.00	2.008 - 2.002	Haynes-25/Ta-10W
PR-110	287.84	154.00	2.000 - 1.989	Haynes-25/Ta-10W
PR-111	291.56	154.00	2.001 - 1.991	Haynes-25/Ta-10W
PR-112	365.28	228.35	1.999 - 1.986	Haynes-25/Ta-10W
PR-113	288.13	147.90	2.002 - 1.986	Haynes-25/Ta-10W
PR-114	291.15	154.00	2.009 - 2.002	Haynes-25/Ta-10W

* Capsule Nos. T-1, T-2, and T-3 were delivered and impacted, however, these were process development capsules for which no data was collected.

0310547174

~~CONFIDENTIAL~~

Figure IV-14. Creep Test Specimen Drawing

-126-

~~CONFIDENTIAL~~

0310547174

~~CONFIDENTIAL~~

~~DECLASSIFIED~~

b. Creep Test Units. Two Haynes-25 and two Ta-10W creep test units were made. Both Ta-10W units contained weld rings, but only one (PCS-2) had a fuel retainer plate. One Haynes-25 liner unit with weld ring and fuel plate was fabricated (PCS-3). The other was made from outer impact shell hemispheres (PCS-4). No weld ring or fuel retainer plate was used in this unit. Non-destructive inspection and evaluation showed that these specimens satisfied design requirements.

3. Summary

Test specimens included:

- (a) 22 for impact testing,
- (b) 3 burst test,
- (c) 4 creep test liners.

~~CONFIDENTIAL~~

~~DECLASSIFIED~~

0315087000
~~CONFIDENTIAL~~

V. PERFORMANCE TESTING AND EVALUATION

The objective was to establish the characteristics of Haynes-25/Haynes-25 and Haynes-25/Ta-10W capsules. The test program includes:

- (1) Evaluation of bursting strength and creep properties of capsule liners;
- (2) Determination of structural integrity of the complete capsule at high impact velocities.

The test program is still in progress, as originally anticipated. Burst pressure testing is complete. Impact and creep tests are in progress.

A. Details of the Test Program

The test program was jointly established by the Sandia Corporation and Hittman Associates, Inc. A summary of the test program is given in Table V-1. The program is similar to that originally planned, but was modified to reflect changes in test parameters and the availability of additional test specimens.

1. Burst Pressure Testing

These fuel capsules, when used with plutonium fuel, must contain the helium generated by alpha decay. The object of these burst tests was to demonstrate that the spherical capsule liners would contain pressures far in excess of design requirements. These tests were limited to the burst strength of the inner liner and its weld joints at normal operating temperatures. The test in no way simulates the incremental buildup of helium pressure over the normal capsule lifetime.

The burst pressure tests were performed by Hittman Associates, Inc. In each test, the liners were pressurized to the calculated room temperature equivalent pressure required to produce rupture at the capsule operating temperature. Then the liners were externally heated until failure was encountered. The failure pressures were calculated using:

$$p = 2ts/R$$

- 128 -
~~CONFIDENTIAL~~
031712081000

TABLE V-1. SUMMARY OF PERFORMANCE TEST PROGRAM

Test No.	Test Type	Materials		No. of Units Tested	Planned Test Temperature	Planned Test Conditions	
		Liner	Shell			Pressure	Velocity
1	Burst	Ta-10W	none	1	1500°F	4340 psia	---
2	Burst	Haynes-25	none	2	1500°F	3808 psia	---
3	Impact (Test Setup)	Haynes-25	Haynes-25	3	500°F	61.6 psia	365 fps and up
4	Impact	Tantalum	Haynes-25	3	500°F	59.4 psia	365 fps and up
5	Impact	Haynes-25	Haynes-25	4	500°F	61.6 psia	365 fps and up
6	Impact ⁽¹⁾	Tantalum	Haynes-25	5	500°F	59.4 psia	365 fps and up
7	Impact ⁽²⁾	Haynes-25	Haynes-25	7	500°F	61.6 psia	365 fps and up
8	Creep	Tantalum	none	2	1800°F	step-wise variation	---
9	Creep	Haynes-25	none	2	1500°F	step-wise variation	---

(1) Prior to impact testing, these specimens were held at a temperature of 1800°F for 1000 hours to simulate shelf life

(2) Prior to impact testing, these specimens were held at a temperature of 1500°F for 1000 hours to simulate shelf life

CONFIDENTIAL

-129-

CONFIDENTIAL

0315587030

~~CONFIDENTIAL~~

where:

p = pressure, psi
t = wall thickness, in
s = tensile strength, psi
R = radius of the sphere, in

The calculated burst pressure of the Haynes-25 liner at the ultimate strength is 3808 psia at 1500°F. This corresponds to a fill pressure of 1030 psia at 70°F. The Ta-10W sphere burst pressure was calculated to be 4340 psia at 1500°F, or a fill pressure of 1174 psia at 70°F.

2. Impact Testing

The reference capsule system is designed to burn up during normal reentry from an orbital position. However, for a low altitude missile abort (below 100,000 feet), the capsule could fall free and impact without reentry heating. The calculated terminal velocity for the capsule is 335 feet per second. Impact against a block of granite was selected as the most stringent impact medium. The surface temperature of the capsule, after being cooled during the free fall, was calculated to be 500°F.

In a superalloy system, like the Haynes-25/Haynes-25 design, a breach of the inner liner would not constitute capsule failure as long as the outer shell was intact. Similarly, a breach in the outer shell without damage to the inner liner would not be a failure. In the superalloy/refractory system, a different case exists. Here, a breach in the superalloy outer shell could result in failure of the refractory liner by oxidation. Similarly, the outer Haynes-25 shell is not compatible with the fuel at high temperatures and could not contain high pressures.

In the first part of the impact test program, the capsules of both systems were impacted slightly above terminal velocity. These tests demonstrated the primary objective of capsule integrity. Subsequent impact tests were then made at incremental increases above terminal velocity to evaluate deformation characteristics and failure mode.

0315587030
~~CONFIDENTIAL~~

~~CONFIDENTIAL~~
REF ID: A66011

The impact tests are being performed by Sandia Corporation. They consist of impacting a solid granite block traveling on a sled against a stationary capsule held at the calculated impact temperature. Two types of impact tests are being run. The first consists of impacting specimens of both capsule systems in the as-fabricated condition. These have been completed. The second will impact test capsule specimens of both systems after a simulated shelf life of 1000 hours at operating temperatures.

3. Creep Testing

These tests will evaluate the long term ability of the capsule liners to withstand helium pressure. Two liners of each capsule system are being tested. The tests are being conducted by Westinghouse Astronuclear for Sandia Corporation. They will measure relatively short-term creep rates using a step function of varying pressure to find the point of significant creep (selected as one percent) at the operating temperature of each liner. The specimens will be tested in the as-fabricated condition. The amount of creep will be measured from a grid on the liner wall. The Ta-10W liners will be tested in a high vacuum, and the Haynes-25 liners in ultra-high-purity argon.*

4. Post Test Diagnostic Examination

All of the burst, impact, and creep test specimens are being given a detailed post-test diagnostic examination. This examination has been completed for the burst test specimens. It included visual examination, dimensional inspection where possible, and metallographic examination. Similar diagnostic examinations are being used on the impact specimens as tests are completed. This includes visual and leak testing where necessary by Sandia Corporation, and visual, dye penetrant, helium leak, dimensional analysis, and metallographic examination by Hittman Associates, Inc. A similar evaluation is planned for the creep test units.

* Present plans are to publish an addendum to this report after the creep tests have been completed and evaluated.

-131-
~~CONFIDENTIAL~~

REF ID: A66011

0311507031

~~CONFIDENTIAL~~B. Test Results1. Bursting Pressure Tests

The burst pressure test preparation consisted of:

- (a) The fabricated burst specimens were mated with high pressure extension lines, valves, and fittings for connections to normal high pressure inert gas bottles. This allowed for pressurization of the inside of the specimens to 2200 psig,
- (b) The specimens were fitted with thermocouple wires for surface temperature measurements during testing. Two thermocouples were spot welded on each specimen; one at the bottom of the sphere and one approximately 10° below the circumferential weld joint;
- (c) The specimen was placed in a heavy walled Hastelloy-C containment vessel,
- (d) The vessel was placed in a resistance furnace;
- (e) The high pressure lines and the thermocouple connections were brought out of the containment vessel through special fittings.

This protected the specimens against oxidation. During the tests, the specimen temperature was monitored by a potentiometer, and the pressure checked by use of a special high pressure gas gauge. Figure V-1 shows one unit prior to testing.

The test procedure consisted of pressurizing the inside of the specimen while at room temperature. The capsule fill line was then sealed by a valve, and the specimen brought to temperature. The increases in temperature and pressure were monitored until failure occurred.

Table V-2 summarizes the results of the three burst tests. The post test condition is shown in Figure V-2. The first Haynes-25 specimen was used for test setup and checkout. It was assembled within the containment

0311507031

~~CONFIDENTIAL~~

~~CONFIDENTIAL~~

Figure V-1. Creep-Burst Test Specimen

~~CONFIDENTIAL~~

TABLE V-2 RESULTS OF BURST PRESSURE TESTS

<u>Test No</u>	<u>Specimen Type</u>	<u>Fill Pressures</u> <u>(psig at 70°F)</u>	<u>Burst</u> <u>Pressure</u> <u>(psig)</u>	<u>Burst</u> <u>Temp.</u> <u>(°F)</u>	<u>Test Time</u> <u>(min)</u>	<u>Specimen Condition</u>
1	Ta-10W	1174	2330	1190	51	Top end blown off
2a	Haynes-25	1000	2000	1710	78	Small burst hole on top of sphere
2b	Haynes-25	1030	2200	1650	63	Top end blown off

~~CONFIDENTIAL~~

~~CONFIDENTIAL~~

CONFIDENTIAL

Test 1
Haynes-25

Test 2
Haynes-25

Test 3
Ta-10W

Figure V-2. Burst Test Specimen

CONFIDENTIAL

0315587030

~~CONFIDENTIAL~~

vessel, pressurized to 100 psig, and heated to 1500°F to check the thermocouples, furnace, pressurization, and containment characteristics of the setup. The specimen was then cooled to room temperature, and the actual bursting pressure test was performed. The liner was pressurized to 1000 psig with ultra-high-purity argon at 70°F prior to heating. Failure was observed as a sudden decrease in internal gas pressure when the specimen reached 1710°F at a pressure of 2000 psig.

Inspection of the tested specimen showed that bursting occurred in a localized area on the end of the specimen opposite the fill tube (see the top specimen in Figure V-2). Detailed visual, dye penetrant, and metallographic inspection showed that the end which failed contained many fine surface cracks as shown in Figure V-3 (View A). These cracks migrated into the wall of the sphere in an intergranular pattern. The actual failure occurred by propagation of intergranular cracks through the wall as shown in View B of Figure V-3. Surface cracking and fracture were not evident in the circumferential weld area, which is shown in View C of Figure V-3. Dimensional measurements of the tested capsule liner showed that the specimen had expanded about 0.090 inch in diameter from pole to pole at the failure area, while decreasing by about 0.030 inch in diameter in the area of the circumferential weld (90° from the failure crack). This specimen contained no weld ring, but was simply circumferentially welded at the joint. Specimen growth in the pole to pole areas and the fine surface cracking suggest a short term creep type failure.

The second burst pressure test was also run on a Haynes-25 specimen. The liner was sealed in the containment vessel and pressurized to 1030 psig at 70°F with ultra-high-pure argon. With the capsule liner sealed under pressure, the temperature was raised until failure occurred at 2200 psig and 1650°F. In this test, the end of the sphere opposite the fill tube was blown away. The condition is shown as the middle specimen of Figure V-2. Fracture occurred near the circumferential weld area over two-thirds of the surface, and about one-half inch above the weld joint in the other one-third of the surface. As with the first specimen, failure appeared to result from yielding at the grain boundaries. The top half of the sphere had many micro-fissures. Detailed visual and metallographic examination showed this cracking to be similar to that observed for the first specimen.

-136

0317128136

~~CONFIDENTIAL~~

~~CONFIDENTIAL~~

DECLASSIFIED

View A - Normal Area of Wall
Test 1 - Haynes-25

View B - Burst Area of Wall
Test 1 - Haynes-25

View C - Circumferential Weld Area
Test 1 - Haynes-25

View D - Burst Area of Wall
Test 3 - Ta-10W

Figure V-3. Photomicrographs Burst Test Specimens

~~CONFIDENTIAL~~

DECLASSIFIED

0315000000
~~CONFIDENTIAL~~

The third test was run on a Ta-10W specimen in the same manner as the second Haynes-25 unit. Liner failure occurred at 2330 psig and 1190°F. The condition of the refractory liner was similar to the Haynes-25 unit. It is shown in the bottom specimen of Figure V-2. Photomicrographs of the fractured section of the wall are shown in Figure V-3, (View D). Note the fine intergranular cracking in the fracture tip. The intergranular surface fissures were again evident, but only in the fractured area.

2. Impact Tests

Three variations exist in the Haynes-25/Haynes-25 units. The first three were development capsules tested in the as-fabricated condition. The next four were production capsules tested in the as-fabricated condition. The remaining seven are being heat treated to simulate shelf-life prior to impact testing.

Two specimen variations exist for the Haynes-25/Ta-10W impact series. The first three units were production capsules tested in the as-fabricated condition. The remaining seven are being heat treated.

Impact testing consists of:

- (a) Specimens are fitted with micro-strain gauges and a thermocouple;
- (b) The capsule is placed in the center of a rocket sled track on a thin wire stand;
- (c) A furnace is placed around the capsule and used to heat the specimen to 500°F;
- (d) A rocket sled carrying a solid granite block is positioned up the track from the capsule;
- (e) When the specimen has reached the impact temperature, the furnace is raised, the rockets fired, and the granite block impacted against the capsule as the sled travels down range;
- (f) After impact, the capsule is caught in a catcher placed down range and parallel to the track.

0317200000
~~CONFIDENTIAL~~

~~CONFIDENTIAL~~
~~CONFIDENTIAL~~

During the actual impact, temperature, high speed motion pictures, and strain gauge measurements are taken. After impact, the capsule is inspected by visual, dye penetrant, and helium leak test techniques. Test results are summarized in Table V-3. Figure V-4 shows the first impacted capsule and an as-fabricated capsule prior to destructive analysis.

a. Development Haynes-25/Haynes-25 Capsules. All three development units survived the tests with no indications of fracture, cracking, leakage, or other detrimental characteristics. Figures V-5 and V-6 show the capsules sectioned pole to pole. An as-fabricated Haynes-25/Haynes-25 development phase capsule is shown for comparison. The order from top to bottom is of increasing impact velocity. The photomicrographs of Figure V-7 are typical sections of the highest velocity impact specimen of this series, Capsule No. T-2. The strength and integrity of the weld joints on both the inner liner and outer shell appeared excellent.

b. As-Fabricated Haynes-25/Haynes-25 Capsules. All units survived the tests as evaluated by visual and dye penetrant methods. One capsule, PR-5, had a very small helium leak when tested by Sandia Corporation. Subsequent retest at Hittman Associates indicated no leakage. (This capsule missed the specimen catcher after impact.) Visual inspection following testing showed several deep gouges. The area which indicated a leak was in one of these.

Following visual, dye penetrant, and helium testing, the capsules were destructively evaluated by visual, dimensional, dye penetrant, and metallographic techniques. The four capsules, sectioned pole to pole are shown in Figures V-8 and V-9. The order from top to bottom is in increasing impact velocities. The first two capsules have no indications of crack, fracture, leakage, or other detrimental conditions. The third capsule in the series (PR-5) had one questionable area near the fuel fill hole of the inner liner. There was a fine crack on the inside surface in the weld joint. This was helium leak checked and metallographically examined. The crack did not breach the wall. This is the capsule which missed the catcher during the impact test. It appears to have been re-impacted several times as it was hurled down the test track. As shown in Figure V-8, the outer shell was dented above the fuel joint of the inner liner.

-139-
~~CONFIDENTIAL~~
~~CONFIDENTIAL~~

TABLE V-3. RESULTS OF IMPACT TESTS

<u>Test No.</u>	<u>Specimen No.</u>	<u>Capsule System</u>	<u>Impact Temp. (°F)</u>	<u>Impact Velocity (ft/sec)</u>	<u>Post Test Condition</u>
T-1**	T-1	Haynes-25/ Haynes-25	500	370	Good
T-2**	T-2	Haynes-25/ Haynes-25	495	410	Good
T-3**	T-3	Haynes-25/ Haynes-25	500	370	Good
R-1	PR-3	Haynes-25/ Haynes-25	495	429	Good
R-2	PR-4	Haynes-25/ Haynes-25	500	452	Good
R-3	PR-5	Haynes-25/ Haynes-25	465	528	Good, small helium leak 10^{-8} std cc/sec
R-4	PR-6	Haynes-25/ Haynes-25	475	561	Good
R-5	PR-106	Haynes-25/ Ta-10W	500	327	Good
R-6	PR-109	Haynes-25/ Ta-10W	495	400	Good
R-7	PR-108	Haynes-25/ Ta-10W	375*	457	Good, small helium leak 10^{-6} std cc/sec

*Low due to error on temperature setting.

**Used to check out test facility.

~~CONFIDENTIAL~~

~~RESTRICTED~~

T-1 Impact Test Specimen

As-fabricated Capsule

Figure V-4. Development Phase Capsules Haynes-25/Haynes-25 System

~~CONFIDENTIAL~~

~~RESTRICTED~~

031558733

~~CONFIDENTIAL~~

Inner Liners

Outer Shells

Figure V-5. Surface Views of Development Phase Impact Specimens
Haynes-25/Haynes-25 System (Pole to Pole Section)

-142-

03704133

~~CONFIDENTIAL~~

~~CONFIDENTIAL~~

DECLASSIFIED

Figure V-6. Internal Views of Development Phase Impact Specimens
Haynes-25/Haynes-25 System (Pole to Pole Section)

~~CONFIDENTIAL~~

DECLASSIFIED

0314507070

CONFIDENTIAL

Circumferential Weld Area

Area at Maximum Bend

Inner Liner Sections

Circumferential Weld Area

Area at Maximum Bend

Outer Shell Sections

Figure V-7. Photomicrographs of Development Phase Impact Specimens
Haynes-25/Haynes-25 System (T-2 Series)

0314507070

CONFIDENTIAL

~~CONFIDENTIAL~~

RECORDED

Inner Liners

Outer Shells

Figure V-8. Surface Views of Production Phase Impact Specimens
Haynes-25/Haynes-25 System (Pole to Pole Section)

~~CONFIDENTIAL~~

RECORDED

0315587000
~~CONFIDENTIAL~~

Figure V-9. Internal Views of Production Phase Impact Specimens
Haynes-25/Haynes-25 System (Pole to Pole Section)

0315587000
~~CONFIDENTIAL~~

~~CONFIDENTIAL~~
REF ID: A66031

The fourth capsule, PR-6, impacted at a velocity of 561 feet per second, and had a breach of the liner wall. The outer shell was free of any crack, fracture, or leakage. The inner liner crack is in the flat section just beyond the maximum bend angle, as shown in the inside view in Figure V-9. It occurred adjacent to the spacer wire used to separate the inner liner and the outer shell, as shown in Figure V-10. Surface cracks were evident in the fuel fill weld; this time on both the inside and outside liner surfaces. However, visual and metallographic examination indicated that these cracks did not penetrate the liner wall. The series B photomicrographs of Figure V-10 show views of the circumferential weld and maximum bend angles of the inner liner and outer shell. Note the heavy deformation of the circumferential weld joint on the liner. No fracture or tearing is evident at the sharp cleavage angle. The inner liner maximum bend view shows the fractured area, with the spacer wire visible at the crack surface. Other bend areas of this liner are crack free.

c. As-Fabricated Haynes-25/Ta-10W Capsules. In the last series of as-fabricated capsule tests, three Haynes-25/Ta-10W capsules were impacted at velocities from 327 to 457 feet per second. External inspection of the impacted capsules showed no indications of fracture, cracking or other detrimental characteristics. Only the specimen impacted at 457 feet per second gave any indication of helium leakage (Capsule No. PR-108). A leak of 10^{-6} standard cubic centimeters of helium per second occurred near the atmosphere fill hole at the end opposite impact.

After the usual non-destructive inspection, the capsules were sectioned and inspected by visual, dye penetrant, dimensional, and metallographic examination. Only the first two capsules (PR-106 and PR-109) have been destructively evaluated. The pole to pole sections of these are shown in Figures V-11 and V-12. The outer surface view of PR-109 shows the strain gauges attached near the circumferential weld on the outer shell. Metallographic analysis of PR-106 showed the start of fracture cracks at the fuel fill joint on the inner liner. None of these cracks breached the liner wall. The areas are shown in Figure V-13 (View A). No other areas, including the liner circumferential and atmosphere weld areas, and the outer shell, showed indications of detrimental conditions. Examination of PR-109 showed that the

-147-
~~CONFIDENTIAL~~
REF ID: A66031

031507838

~~CONFIDENTIAL~~

Circumferential Weld Area

Area of Maximum Bend
(Breached Area)

Inner Liner Sections

Circumferential Weld Area

Area of Maximum Bend

Outer Shell Sections

Figure V-10. Photomicrographs of Production Phase Impact Specimens
Haynes-25/Haynes-25 System (PR-6 Series)

037028158
~~CONFIDENTIAL~~

~~CONFIDENTIAL~~

~~RECORDED~~

Ta-10W Inner Liners

Haynes-25
Outer Shells

Figure V-11. Surface Views of Production Phase Impact Specimens
Haynes-25/Ta-10W System (Pole to Pole Section)

~~CONFIDENTIAL~~

~~RECORDED~~

031508733
~~CONFIDENTIAL~~

Ta-10W Inner Liners

Haynes-25
Outer Shells

Figure V-12. Internal Views of Production Phase Impact Specimens
Haynes-25/Ta-10W System (Pole to Pole Section)

-150-

CONFIDENTIAL

031508733

~~CONFIDENTIAL~~

REF ID: A62610

View A

View B

Figure V-13. Photomicrograph Composite of Fuel Plug Area
on Inner Liner of Specimens PR-106 & PR-109
Haynes-25/Ta-10W System

~~CONFIDENTIAL~~

REF ID: A62610

0315581000
~~CONFIDENTIAL~~

cracks observed in the previous specimen had progressed until fracture occurred at the fuel fill joint. This is shown in View B of Figure V-13. The remaining sections show no indications of detrimental characteristics. Figure V-14 shows typical photomicrographs.

C. Performance Test Evaluation

1. Burst Tests

The calculated burst pressures for the liners are shown in Figures III-37 and III-38. For the two Haynes-25 liners, the experimental points lie on the yield strength burst pressure line as shown in Figure III-37. Only one experimental point was obtained for the Ta-10W liner. As shown in Figure III-38, this point is on the ultimate burst pressure curve. Two conclusions which may be drawn from these limited tests are:

- (a) The strength of the welded joints appear as good as the parent material stock;
- (b) The spherical capsules should contain pressures well above those predicted for the five year capsule life. However, data are limited. The effect of fabrication and thickness variations has not been fully determined.

2. Impact Tests

The impact tests are fifty percent complete. The preliminary results show that the primary objective of capsule structural stability at terminal velocity has been achieved. The spherical capsules exceed performance requirements. The weld joints are strong, which verifies that the spherical geometry can be satisfactorily fabricated. Evaluation of deformation characteristics and mode of failure is continuing.

0317220000
~~CONFIDENTIAL~~

Circumferential Weld Area

Area at Maximum Bend

Ta-10W Inner Liner Sections

Circumferential Weld Area

Area at Maximum Bend

Haynes-25 Outer Shell Sections

Figure V-14. Photomicrographs of Production Phase Impact Specimens
Haynes-25/Ta-10W System (PR-109 Series)

CONFIDENTIAL

-153-

CONFIDENTIAL

03115087078

~~CONFIDENTIAL~~REFERENCES

1. Lockheed Letter LMSC/A792838A, "Nimbus B Revised Preliminary Sequence of Events," (February 28, 1966).
2. Lockheed Data on Thorad/Agena D Dynamic Nominal Trajectory.
3. Morrison, "Design Data for Aeronautics and Astronautics," John Wiley and Sons, Inc., p. 207, (1962).
4. Remmler, "Tumbling Bodies Entering the Atmosphere," ARS Journal, Vol. 32, No. 1.
5. Hittman Associates, Inc., Under Contract NAS5-9548, T. D. No. 48, "Planar Generator Steady State and Reentry Thermal Analyses," (October 28, 1966).
6. Lyon, W. C., HIT-162, "The TAP-3 Program," (April 1965).
7. Marshall, B. W., SC-RR-65-615, "An Experimental Study of the Effect of Oxygen on Tantalum Ablation in a Hyperthermal Plasma Tunnel," (April 1966).
8. McAdams, Heat Transmission, McGraw Hill, Third Edition, pp. 265 and 266.
9. Boelter, Cherry, Johnson and Martinelli, "Heat Transfer Notes," University of California Press, Vol. II, (1948).
10. Rajnak and Hauser, "Plastic Wave Propagation in Rods," Symposium On Dynamic Behavior of Materials, ASTM Publication No. 336, pp. 167-179, (1962).
11. Provided by H. Togami of Sandia Corporation.
12. Bell, "The Initiation of Finite Amplitude Waves in Annealed Metals," Springer-Verlag, pp. 165-182, (1964).
13. Johnson and Miller, "Plasticity for Mechanical Engineers," Van Nostrand, (1962).
14. Goldsmith, W., Impact the Theory and Physical Behavior of Colliding Solids, Edward Arnold, Ltd., London, England, (1960).

03112287034

~~CONFIDENTIAL~~

~~CONFIDENTIAL~~

DECLASSIFIED

APPENDIX A

COMPUTER LOGIC DIAGRAMS

~~CONFIDENTIAL~~

DECLASSIFIED

03150701

~~CONFIDENTIAL~~

Figure A-1. Flow Logic Diagram for CAPSPE Computer Program

03170201

~~CONFIDENTIAL~~

~~CONFIDENTIAL~~

HITTMAN AERODYNAMIC CODE (HAC)
FLOW LOGIC DIAGRAM

Figure A-2. Flow Logic Diagram for HAC Computer Program

~~CONFIDENTIAL~~

~~CONFIDENTIAL~~

Figure A-3. Flow Logic Diagram for LMCAP Computer Program

~~CONFIDENTIAL~~

~~CONFIDENTIAL~~

APPENDIX B

OXIDATION OF Ta-10%W ALLOY UNDER REENTRY CONDITIONS

I. DISCUSSION OF SANDIA CORPORATION EFFORT

B. W. Marshall of Sandia Corporation has derived (Reference B-1) an expression for the tantalum recession rate. It is not possible to follow this derivation and obtain the reported coefficients. However, he also reported a number of tests to check his predictions. These tests, performed in North American Aviation's arc-powered hyperthermal wind tunnel, yielded results close to those predicted.

Marshall treated the general reaction

He assumed that under reentry conditions the reaction was limited by the availability of oxygen and showed that rate of recession of the tantalum surface is:

$$\frac{\Delta L}{\Delta \theta} \propto \left(\frac{2X}{Y} \right) \left(\frac{\text{A. wt. of Ta}}{\text{Density of Ta}} \right) \quad (\text{B-2})$$

In his initial correlation, he assumed that the product Ta_XO_Y was Ta_2O_5 , the stable oxide of tantalum. He found, however, that extremely close correlation was obtained if he assumed the oxidation product to be "TaO." He explains this by referring to a phase diagram study of the Ta-O system by Dubrovskaya and associates, who reported "the Ta-O system has a simple eutectic equilibrium diagram, the eutectic point being close in composition to TaO." Presumably, the actual reaction taking place during the wind tunnel tests was the oxidation of tantalum to Ta_2O_5 , the formation of a Ta_2O_5 -Ta eutectic melt of the composition analogous to "TaO," and the sweeping of this liquid to a cooler part of the test specimen where it resolidified and underwent further oxidation. The experimental evidence, including limited chemical analyses,

~~CONFIDENTIAL~~

support this hypothesis. Therefore, the most accurate predictions of tantalum oxidation can be obtained by assuming Ta_XO_Y in Equation (B-1) to be TaO.

Marshall's equation then becomes, in inches/second:

$$\frac{\Delta L}{\Delta \theta} = 0.00545 \Delta X_O \left[\frac{P_{t_2}}{R_e} \right]^{1/2} \quad T > 3800^\circ F \quad (B-3)$$

where:

ΔX_O = mass fraction of oxygen in the gas

P_{t_2} = total pressure behind the normal shock wave, lb/ft²

R_e = effective nose radius, ft

II. EFFECT OF ADDITION OF Ta-10%W ON THE OXIDATION OF TANTALUM

Schmidt (Reference B-2) and Kubaschewski and Hopkins (Reference B-3) have reported the effect of tungsten addition on the oxidation behavior of tantalum. Both these authors refer to work performed by Jaffe and associates at Battelle Memorial Institute. The effect of Ta-10%W on the oxidation rate of tantalum is small, as seen in Figure B-1 (Reference B-2).

Marshall's equation can be modified by considering the oxidation reactions taking place in the alloy and comparing them with the pure metal. The following assumptions are necessary:

- (1) In the pure metal, material is removed as Ta_2O_5 and as Ta with a eutectic composition close to "TaO" so that the effective reaction can be written.

Figure B-1. One Hour Weight Gain of Ta-W Alloys in Air
(Reference 2)

- (2) In the alloy, the metal components oxidize individually, the tantalum as above, and tungsten by:

Since Ta-10W contains close to 10 atomic percent tungsten, this value was used. The recession rate for the alloy becomes:

$$\begin{aligned} \frac{\Delta L}{\Delta \theta} \text{ alloy} &\propto \left[0.9 \left(\frac{2 \text{ at. wt. Ta}}{\text{density of alloy}} \right) + 0.1 \left(\frac{2}{3} \frac{\text{at. wt. of W}}{\text{density of alloy}} \right) \right] \\ &\propto \left[0.9 \left(\frac{2 \times 180.948}{1050} \right) + 0.1 \left(\frac{2 \times 183.85}{3 \times 1050} \right) \right] \\ &\propto 0.322 \end{aligned} \quad (B-6)$$

By comparison Equation (B-2) can be evaluated as:

$$\begin{aligned} \frac{\Delta L_{Ta}}{\Delta \theta} &\propto \left[\frac{2 \times \text{at. wt. Ta}}{Y \text{ density of Ta}} \frac{2 (180.948)}{1037} \right] \\ &\propto 0.348 \end{aligned}$$

Therefore, if Marshall's expression is correct, the predicted recession rate for Ta-10W is:

$$\frac{\Delta L}{\Delta \theta} = 0.00504 \Delta X_o \left[\frac{P_{t2}}{R_e} \right]^{1/2} \quad T > 3800^\circ F \quad (B-7)$$

~~CONFIDENTIAL~~

UNCLASSIFIED

APPENDIX B

REFERENCES

1. Marshall, B. W., "An Experimental Study of the Effect of Oxygen on Tantalum Ablation in a Hyperthermal Plasma Tunnel," Sandia Corporation Report, SC-RR-65-615, (April 1966).
2. Schmidt, F. F., "Tantalum and Tantalum Alloys," DMIC Report 133, (July 1960).
3. Kubaschewski, O., and B. E. Hopkins, Oxidation of Metals and Alloys, Second Edition, London:Butterworths, (1962).

~~CONFIDENTIAL~~

UNCLASSIFIED