CONF-710938--

MASTER

RECEIVED BY DTIC DEC 20 1971

XI International Conference on
THERMAL CONDUCTIVITY

SEPTEMBER 28 – OCTOBER 1, 1971

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency Thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

DISCLAIMER

Portions of this document may be illegible in electronic image products. Images are produced from the best available original document.

THE THERMAL CONDUCTIVITY OF EIGHT AEROSPACE METALS AND ALLOYS

R. P. Tye, R. W. Hayden and S. C. Spinney⁽¹⁾
Dynatech R/D Company
Cambridge, Massachusetts 02139

In association with the requirement for reliable design data for materials used in conjunction with nuclear energy applications, thermal conductivity determinations have been carried out over all or parts of the approximate temperature range 100 to 1200K on eight metals. In all, eight samples of each material in its appropriate commercial form were studied in order to obtain sufficient data to provide a valid statistical curve for the thermal conductivity behaviour.

The eight materials and the temperature range studied were as follows:

1. A hot pressed beryllium approximately 98.4% pure, 90 to 600K
2. A titanium alloy containing 5% Al and 2.5% Sn, 90 to 600K
3. An Inconel 718 in the unannealed condition, 90 to 1200K
4. An iron based superalloy A 286, 90 to 700K
5. A Molybdenum TZM alloy containing approximately 0.5 Ti, 90 to 1200K.
6. A 304 Stainless Steel, 100 to 1100K
7. A 301 Stainless Steel, 100 to 700K
8. A T6061 aluminum alloy, 100 to 600K

The materials were supplied in rod form except for the 301 Stainless which was in sheet form and this was fabricated into rod form using special end pieces. Determinations were made by the axial rod method [1]² and, in all, three different apparatus were used. In addition, electrical resistivity measurements were carried out over the required temperature range, plus determinations at 4.2K to help characterise the materials.

The thermal conductivity instruments used were checked out using both a high purity copper for the temperature range 100 to 600K and Armco Iron for the range 100 to 1100K. The latter material was a piece cut from the original Powell 1934 iron [2] and which had been in use as a reference material for many years.

Results will be presented for each material both individually and collectively and compared when possible with other results. The present results verify the claim that an accuracy of ± 2 to $\pm 4\%$ is possible with the instruments as designed and operated and for the conductivity range covered. The results may be summarized as follows:

1. The hot-pressed beryllium consisted of two distinct "lots", one having a resistivity ratio between 293 and 4.2K of 6.6, and the other 4.6. The former material exhibited a maximum in λ at approximately 118K with a value of $330 \text{ W m}^{-1} \text{ K}^{-1}$ and the latter at 140K with a value of $260 \text{ W m}^{-1} \text{ K}^{-1}$. Within the two lots differences in the values of λ and ρ from the means are due to slight compositional differences. Above 300K the relative differences are slight and the values are in good agreement with those reported previously [1,3] for this material.
2. The titanium alloy showed very small variations in electrical resistivity and all thermal conductivity values were well within 4% of a mean line drawn through the experimental points. The values are in excellent agreement over the range 100 to 300K with those of Hust et al [4] for the same nominal composition and in good agreement above 300K with published data for similar alloys [5,6].
3. For the Inconel 718 all data points were within $\pm 3\%$ of a mean line drawn through them and the material was very reproducible in terms of ρ . Over the range 100 to 300K the results for λ are again in excellent agreement with Hust et al [4].

¹ Manager, Measurements Laboratory, Engineering Aide and Project Manager, respectively.

² Numbers in parenthesis refer to references at end of paper.

4. The A 286 alloy appeared to be a material which is very reproducible in its thermal and electrical transport properties.

5. The TZM Molybdenum alloy increases from approximately $102 \text{ W m}^{-1} \text{ K}^{-1}$ at 100K to a clearly defined maximum of approximately $119 \text{ W m}^{-1} \text{ K}^{-1}$ at 340K and then continues to decrease to $108 \text{ W m}^{-1} \text{ K}^{-1}$ at 1100K. All experimental points were well within $\pm 2\%$ of a mean curve.

6. The 304 stainless steel was very uniform in properties and the mean thermal conductivity curve obtained can be compared with the TPRC recommended curve for this type of material [7]. Over the range 100 to 500K the differences between the curves are between 1 and 2% while up to 1100K the differences are less than 3%.

7. Both the 301 stainless steel and the aluminum alloy were reproducible but were found to be unstable in their original "as supplied state" at temperatures slightly above those required of the original programme. Results will be presented to indicate the changes obtained on heat treatment. In both cases the value of the derived Lorenz Numbers were found to remain unchanged after heating.

ACKNOWLEDGEMENTS

The author wishes to thank Dr. R. Shollenberger of Westinghouse Electric Corp., Astronuclear Laboratories for permission to present these results informally.

REFERENCES

1. Tye, R. P. and Quinn, J. E. (1964) Proc. 4th Symposium on Thermophysical Properties. A.S.M.E., New York, pp. 144-149.
2. Powell, R. W. (1934) Proc. Phys. Soc. 46, 659.
3. Tye, R. P. and Brazel, J. P. (1970) Rev. Int. Hautes. Temper. et Refract., 7, 326.
4. Hust, J. G., Powell, R. L. and Weitzel, D. H. (1969), NBS Report - 9732, p. 188.
5. Powell, R. W. and Tye, R. P. (1960) J. Less. Common Metals, 3, 226.
6. Deem, H. W., Wood, W. D., and Lucks, C. F. (1958) Trans. Metall. Soc. AIME, 212, 520.
7. Thermophysical Properties of Matter, Volume 1, Eds. Touloukian, Y. S., Powell, R. W., Ho, C. Y., and Klemens, P. G., Plenum Press, New York, 1970.