LEGAL NOTICE

This report was prepared as an account of Government sponsored work. Neither the United States, nor the Commission, nor any person acting on behalf of the Commission:

A. Makes any warranty or representation, expressed or implied, with respect to the accuracy, completeness, or usefulness of the information contained in this report, or that the use of any information, apparatus, method, or process disclosed in this report may not infringe privately owned rights; or

B. Assumes any liabilities with respect to the use of, or for damages resulting from the use of any information, apparatus, method, or process disclosed in this report.

As used in the above, "person acting on behalf of the Commission" includes any employee or contractor of the Commission, or employee of such contractor, to the extent that such employee or contractor of the Commission, or employee of such contractor prepares, disseminates, or provides access to, any information pursuant to his employment or contract with the Commission, or his employment with such contractor.

ANL-7606

Reactor Technology

ARGONNE NATIONAL LABORATORY

9700 South Cass Avenue

Argonne, Illinois 60439

REACTOR DEVELOPMENT PROGRAM PROGRESS REPORT

August 1969

Robert B. Duffield, Laboratory Director
Stephen Lawroski, Associate Laboratory Director

Division

Director

Chemical Engineering

R. C. Vogel

EBR-II Project

M. Levenson

Metallurgy

M. V. Nevitt

Reactor Engineering

L. J. Koch

Reactor Physics

R. Avery

Report coordinated by

A. Glassner and A. D. Rossin

Issued September 26, 1969

fly

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency Thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

DISCLAIMER

Portions of this document may be illegible in electronic image products. Images are produced from the best available original document.

FOREWORD

The Reactor Development Program Progress Report, issued monthly, is intended to be a means of reporting those items of significant technical progress which have occurred in both the specific reactor projects and the general engineering research and development programs. The report is organized in accordance with budget activities in a way which, it is hoped, gives the clearest, most logical overall view of progress. Since the intent is to report only items of significant progress, not all activities are reported each month. In order to issue this report as soon as possible after the end of the month editorial work must necessarily be limited. Also, since this is an informal progress report, the results and data presented should be understood to be preliminary and subject to change unless otherwise stated.

The issuance of these reports is not intended to constitute publication in any sense of the word. Final results either will be submitted for publication in regular professional journals or will be published in the form of ANL topical reports.

The last six reports issued
in this series are:

January 1969	ANL-7548
February 1969	ANL-7553
March 1969	ANL-7561
April-May 1969	ANL-7577
June 1969	ANL-7581
July 1969	ANL-7595

REACTOR DEVELOPMENT PROGRAM

Highlights of Project Activities for August 1969

EBR-II

The reactor was operated for 1120 MWd from July 21 through August 20, raising its cumulated operation to 28,194 MWd.

Examination of 16 encapsulated Mark-II elements irradiated to ~4-at. % burnup in EBR-II indicated that the claddings were intact and that there was no jacket strain. Samples of gas taken by puncturing the plenums of six of the elements were free from fission-product isotopes. Three subassemblies containing unencapsulated Mark-II elements are being irradiated in the reactor. The elements in one of the subassemblies will be examined at 2-at. % burnup. Burnup as of August 20 was approximately 0.6 at. %.

Rod-drop experimental data from various reactor runs are being analyzed using the AIROS dynamic-simulation program. AIROS-computed results for rod-drop data from Runs 33A and 36A were found to be in excellent agreement with the experimental data.

ZPR-3

The reactor irradiations in Assembly 57 which were required for the measurement of the capture-to-fission ratio in Pu-239 by the reactivity reaction-rate method have been completed. Extended high-flux operation was required to produce isotopic changes in high-purity foils in order to yield an independent determination of alpha for plutonium in this neutron spectrum.

ZPR-6 and -9

With the completion of final checkout of the exhaust fan, all necessary AEC and Laboratory surveillance and review requirements have been met; the facilities are now ready for approval for plutonium operation. Renewed operation with uranium has been authorized and loading of Assembly 6A has begun for ZPR-6. It will be used initially for the measurement of U-238 and U-235 Doppler effects in a large sodium-voided zone. Additional modifications will subsequently be made to Assembly 6 in order to study pin-type heterogeneity effects.

Assembly 25 is being installed on ZPR-9. This will be a small, uranium-fueled, critical assembly with a central test zone designed to have k_{∞} equal to unity. Measurements in this hard-spectrum zone will provide integral data relevant to the resolution of cross-section uncertainties in Pu-238 and Pu-239.

ZPPR

The ZPPR/FTR-2 transition experiments have been completed, and the radial variations in Pu-239 and U-238 fission and in B-10 capture detector responses have been evaluated experimentally and theoretically. Control- and safety-rod calibrations were made, and a temperature coefficient of $-1.96 \text{ lh}/^{\circ}\text{C}$ was measured. The experimental program was interrupted to perform seal and containment tests of the ZPPR system, which have been computed.

TABLE OF CONTENTS

	<u>Page</u>
I. LIQUID METAL FAST BREEDER REACTORS--CIVILIAN	1
A. Fuel Development--LMFBR	1
1. Oxide	1
B. Physics Development--LMFBR	4
1. Theoretical Reactor Physics	4
2. Experimental Reactor Physics	14
3. ZPR-6 and -9 Operations and Analysis	17
4. ZPR-3 and ZPPR Operations and Analysis	23
C. Component Development--LMFBR	31
1. Sodium Technology Development	31
2. Instrumentation and Control	33
3. Fuel Handling, Vessels and Internals	40
D. Systems and Plant Development	41
1. Plant and Design	41
E. EBR-II--Research and Development	42
1. Instrumented Subassemblies	42
2. Experimental Irradiation and Testing	42
3. Materials-Coolant Compatibility	46
4. Systems Engineering	47
5. Reactor Analysis, Testing and Methods Development	48
6. Driver Fuel Development	62
7. Operation with Failed Fuel	62
F. EBR-II--Operations	72
1. Reactor Plant	72
2. Fuel Cycle Facility	73
PUBLICATIONS	81
II. OTHER FAST REACTORS--OTHER FAST BREEDER REACTORS--FUEL DEVELOPMENT	84
A. Irradiation Effects, Mechanical Properties and Fabrication	84
1. Irradiation Studies of Cladding Alloys	84
B. Coolant Effects on Cladding Alloys	86
1. Carburization and Localized Attack of Stainless Steel	86

TABLE OF CONTENTS

	<u>Page</u>
III. GENERAL REACTOR TECHNOLOGY	89
A. Applied and Reactor Physics Development	89
1. Theoretical Reactor Physics--Research and Development	89
2. Nuclear Data--Research and Development	90
B. Reactor Fuels and Materials Development	92
1. Fuels and Claddings--Research and Development	92
2. Radiation Damage on Structural Materials--Research and Development	99
3. Techniques of Fabrication and Testing--Research and Development	100
4. Engineering Properties of Reactor Materials--Research and Development	101
C. Engineering Development--Research and Development	104
1. Development of Master-Slave Manipulator Systems	104
2. Heat Transfer and Fluid Flow	104
3. Engineering Mechanics	109
D. Chemistry and Chemical Separations	111
1. Fuel Cycle Technology--Research and Development	111
2. General Chemistry and Chemical Engineering--Research and Development	117
3. Sodium Chemistry--Research and Development	118
PUBLICATIONS	120
IV. NUCLEAR SAFETY RESEARCH AND DEVELOPMENT	123
A. LMFBR Safety--Research and Development	123
1. Accident Analysis and Safety Evaluation	123
2. Coolant Dynamics	124
3. Core Structural Safety	127
4. Materials Behavior and Energy Transfer	127
5. Fast Reactor Safety Test Facility Study	128
6. Violent Boiling	132
PUBLICATIONS	134
PUBLICATIONS--GENERAL	134

I. LIQUID METAL FAST BREEDER REACTORS--CIVILIAN

A. Fuel Development--LMFBR

1. Oxide

a. Fuel Studies

(i) Fuel Element Performance (L. A. Neimark and F. L. Brown)

Last Reported: ANL-7595, pp. 1-2 (July 1969).

(a) Group O-2 Fuel Elements. Element TVOV-1, irradiated to a burnup of approximately 3.6 a/o at a maximum linear power rating of 19.6 kW/ft, was examined metallographically at quarter-length positions along the fuel column. This element contained vibratorily compacted fuel of 77% smear density clad in V-20 w/o Ti. The structure of the lower part of the fuel column of TVOV-1 indicated central fuel melting, characteristic of the other elements in this group (SOV-3, SOV-7, and HOV-15). However, in the higher part of the element, the structure was altered by recrystallization that occurred during low-power operation (two-thirds normal operating power) for $1\frac{1}{2}$ days at the very end of irradiation.

What appears to be a finely dispersed second phase was found adjacent to the central void in the lower portion of the element. The phase was most apparent at the bottom of the unrestructured fuel, which maintained the character of the earlier molten structure. The second phase was not present in the microstructures of the other elements in this series. As shown in Fig. I.A.1, the phase was not evenly distributed throughout the once-molten fuel, but was concentrated adjacent to the central void. Fingers or stringers of the second phase extended radially outward from the central concentration, apparently in association with grain boundaries and with cracks in the solidified fuel. Occasional stringers appeared to penetrate short distances into the columnar-grain region that surrounds the melt region. The association of the second phase with cracks and with grain boundaries suggests that a gas-phase reaction,

Fig. I.A.1. Section near the Bottom of Element TVOV-1, Showing Second Phase in Melt Region That Surrounds the Center Void (10X)

perhaps as a result of oxygen migration, might have occurred while the fuel was solid during the reduced-power operation. The disappearance of the phase from the restructured fuel in the upper portions of the element may be due to a homogenization process during the recrystallization. Electron-microprobe analysis to determine the nature of the second phase is planned.

The inner surface of the V-20 w/o Ti cladding had a 2.5-mil (average) reaction layer, which contained approximately 8% oxygen (see Progress Report for May 1968, ANL-7457, p. 7). This oxygen may be associated with the formation of the second phase in the center of the fuel. However, similar reaction zones have developed during isothermal compatibility tests of unirradiated V-20 w/o Ti alloy in contact with mixed oxide, without the formation of the second phase in the oxide (see Progress Reports for October 1968, ANL-7513, pp. 3-4, and November 1968, ANL-7518, p. 4). Microhardness values (DPH--100g) for the reaction zone in the irradiated cladding ranged from 1145 near the inner surface to 795 near the outer boundary. At the visible boundary of the reaction layer, the hardness of the cladding dropped abruptly to 200 DPH, the average hardness of the irradiated cladding. An unirradiated control specimen of the V-20 w/o Ti alloy had an average hardness of 176 DPH. Intergranular cracks indicated the brittle nature of the oxidized zone. The average thickness of the hardened layer varied from 0.7 mil near the bottom of the fuel column to 2.5 mils near the top, where the maximum cladding temperature was estimated to be 575°C.

No appreciable change in the microstructure of the irradiated V-20 w/o Ti alloy occurred, although the chemical-etching characteristics were altered by irradiation. Structures were readily developed, but not by the same reagents used to etch the unirradiated material.

Cesium was previously identified by microprobe analysis in the grain boundaries of the Type 304 stainless steel cladding of Element SOV-7 (see Progress Report for April-May 1969, ANL-7577, pp. 1-2). A metallographic sample from this element that had been in dry storage for a period of about three months was recently removed for further examination. The inner surface of the cladding had deteriorated in storage because of a loss of cohesion between grains. Many interior, as well as surface, grains were loose or entirely missing from the transverse polished section. The condition of the specimen, shown in Fig. I.A.2, vividly illustrates the extent to which fission products penetrated and damaged the grain boundaries of the cladding. The maximum penetration was 9.4 mils, or nearly 45% of the 21-mil wall.

(b) Groups O-4, O-4A, O-5, and O-5A Fuel Elements. A request for Approval-in-Principle to irradiate Groups O-4, O-4A, O-5, and O-5A fuel elements in EBR-II has been submitted to RDT. These groups

Fig. I.A.2. Type 304 Stainless Steel Cladding at the Upper End of Element SOV-7, Showing Loss of Grains from the Inner Surface due to Intergranular Penetration and Subsequent Reaction of Fission Products (75X)

are intimately tied to ANL's fuel-element modeling studies and to the development of computer codes for prediction of the performance and the lifetime of the elements. The purpose of these groups is both to investigate the mechanisms that cause fuel-element dimensional changes and to test and improve the models in ANL's behavior codes.

The SWELL-2D fuel-element behavior code was used in establishing the test matrix for the O-(4,5) series of experiments. The plenum-to-fuel volume ratio has been selected as the principal design variable, with fuel smear

density and cladding thickness as minor variables. The SWELL-2D code predicts that the plenum-to-fuel volume ratio will play a significant role in fuel-element lifetime at linear power ratings at which appreciable fission gas is released from the fuel, i.e., above approximately 12 kW/ft average. Interestingly, the predicted lifetimes of elements with plenum-to-fuel ratios of 0.5 and 1.0 are nearly the same for linear power ratings up to 16 kW/ft average. If this prediction is correct, fuel elements with shorter plenums could be used in future oxide-fueled reactors.

The O-(4,5) series of experiments will test the predictions of the code by use of a number of plenum-to-fuel volume ratios to determine the component of the diametral strain of the fuel element that is attributable to gas pressure-induced cladding creep. Fuel smear density is being introduced as a variable because of its effect on the temperature distribution in the fuel, on fission-gas release, and on swelling accommodation. By selectively combining the variables of plenum-to-fuel ratio and fuel smear density, these experiments should distinguish between cladding deformation caused by fuel-cladding mechanical interactions and that due to gas-induced cladding creep. The O-4 series will be operated at 11 kW/ft average, and the O-5 series at 16 kW/ft average. The difference in power ratings should enable differentiation between the deformation mechanisms that are associated with fuel and cladding properties under these conditions. This information will be used to refine the deformation models used in our behavior codes.

B. Physics Development--LMFBR

1. Theoretical Reactor Physics

a. General Fast Reactor Physics

(i) Reactor Dynamics (D. A. Meneley)

Last Reported: ANL-7595, pp. 5-7 (July 1969).

A second problem has been studied in the investigation of the importance of including space and energy distortion of flux shapes in the analysis of excursions in very simple oxide-fueled LMFBR systems. The first problem was described in detail in ANL-7595. The initial power level of the reactor just before the excursion begins is an important parameter in the analysis. In Fig. I.B.1 the amplitude function, $\phi(t)$, describes

Fig. I.B.1. Effect of Initial Power Level on Behavior of the Flux Amplitude Function $\phi(t)$

the power in the excursions from ANL-7595 for two cases: the case in which the initial power is P_0 , the full power level of the reactor, and the case in which the initial power is 1% of full power. Both cases were computed with the spatial-kinetics model of the QX1 program, with 26 energy groups, 35 spatial intervals, 15 downscatter groups, and 6 delayed-neutron precursor groups. Convergence criteria were set sufficiently tight that the results represent essentially exact solutions.

At the first power peak (260.43 times full power) the power calculated by point kinetics was 1% lower than the true value, in agreement with the results of the full-initial-power case. The accuracy of the one-percent initial power case was tested by successively tightening convergence criteria. (There is no independent method for testing.) Between

0.070 and 0.085 sec, 14 flux shape functions were used in the fully converged run. The maximum instantaneous inverse period in this range was 946 sec^{-1} ; the minimum value was -813 sec^{-1} . With the use of 100 generation times as a reasonable upper limit for time step length in a finite-difference code,* roughly 400 time steps would be required by such a code to cover the same range. The standard QX1 algorithm includes the time-derivative term for the shape function. The case was rerun with this term omitted; differences

*Carter, N. E., BNWL-738 (1968), p. A-3.

were observed in the sixth decimal place of the amplitude function. This result was not unexpected, since the problem involves very small changes in shape function.

A second problem was run from the same initial conditions as given in ANL-7595. The ramp increase in plutonium concentrations was restricted to the second enrichment region of the core. The rate was adjusted so that the point-kinetics reactivity ramp rate was identical to that in the first problem: \$15.29/sec. The point-kinetics model therefore predicted exactly the same behavior as in the previous case for uniform in-

Fig. I.B.2. Power Shapes Following Nonuniform and Uniform Ramp Insertions

sertion. An indication of the amount of spatial flux shape distortion in the non-uniform case is given by the power shape plot in Fig. I.B.2. (A few points from the uniform perturbation case are plotted for comparison.) Note that the flux in core region 1 is depressed at 0.15 sec due to increased resonance absorption in U-238.

Flux shape distortion in the energy direction due to increased fuel temperature was the main contribution to the disagreement between point and spatial kinetics for the "uniform" problem treated in ANL-7595. In that case the insertion itself introduced spectral distortion which was difficult to separate from that due to the rise of fuel temperature. The centerline flux spectrum in the present case is free from that distortion because the perturbation was only in region 2. The spectra for $t = 0$ and $t = 0.15$ sec, normalized to an equal number of fission neutrons produced, are given in Table I.B.1. As a measure of the spectral distortion coming from the insertion itself, the normalized 26-group centerline flux in the original uniform case was 1.068×10^{-3} at the same temperature rise. By comparing this value with 1.10×10^{-3} for 0.15 sec in Table I.B.1, it can be seen that the main spectral shift comes from the temperature rise.

TABLE I.B.1. Normalized Centerline Spectra

Group	$t = 0 \text{ sec} / \bar{T} = 1300^\circ\text{K}$	$t = 0.15 \text{ sec} / \bar{T} = 2660^\circ\text{K}$	Group	$t = 0 \text{ sec} / \bar{T} = 1300^\circ\text{K}$	$t = 0.15 \text{ sec} / \bar{T} = 2660^\circ\text{K}$
1	2.33×10^{-1}	2.34×10^{-1}	14	3.40	3.42
2	9.39×10^{-1}	9.41×10^{-1}	15	2.07	2.08
3	2.28	2.29	16	1.30	1.30
4	3.04	3.05	17	4.26×10^{-1}	4.25×10^{-1}
5	3.78	3.79	18	1.03	1.02
6	7.43	7.44	19	6.30×10^{-1}	6.03×10^{-1}
7	7.05	7.07	20	2.98×10^{-1}	2.75×10^{-1}
8	9.39	9.42	21	1.21×10^{-1}	1.09×10^{-1}
9	8.97	9.01	22	3.88×10^{-2}	3.33×10^{-2}
10	8.21	8.26	23	1.25×10^{-2}	1.05×10^{-2}
11	6.77	6.81	24	5.24×10^{-3}	4.48×10^{-3}
12	5.67	5.71	25	1.68×10^{-3}	1.45×10^{-3}
13	4.70	4.73	26	1.29×10^{-3}	1.10×10^{-3}

The amplitude functions for point and spatial kinetics in the nonuniform case are shown in Fig. I.B.3. Note that the true flux rises faster even before significant temperature changes have occurred. The uniform-perturbation case did not show this behavior because the only large flux shift was in the energy direction, caused by the temperature rise. In this case the true reactivity insertion rate is higher due to the spatial flux shift. Point kinetics underpredicts the first power peak by 7%. The error in energy release of the point model is 13% at 0.15 sec.

Fig. I.B.3. Behavior of Amplitude Function after \$15/sec Ramp Insertions into Second Enrichment Region

b. Fast Critical Experiments--
Theoretical Support--Idaho

(i) Planning Support
(R. G. Palmer)

Not previously reported.

(a) Pu-239 Doppler Calculations for a Plutonium-Graphite Core.

One of the proposed cores for the physics series in ZPR-3 consists of one-drawer cells containing two columns of Pu-Al plates and fourteen columns of graphite plates. Because of the small expansion characteristics of the ZPR-3 Pu-Al plates, it is necessary that the plutonium Doppler coefficient be zero or negative in order to insure a negative prompt power coefficient. A knowledge of the magnitude and sign of the Pu-239 Doppler coefficient is necessary in these safety considerations. Two core configurations were used in the calculations. In the first, the Pu-Al plates were placed together in the cell; in the second configurations, they were separated by seven columns of graphite. Depleted uranium and lead were both considered as reflector material.

Diffusion-theory calculations were performed with the MACH-1 code using broad-group cross sections generated by MC². Pu-239 fission and capture cross sections in the energy region from 275 eV to 25 keV were calculated from the IDIOT code, and the RABID code was used to obtain the Pu-239 fission and capture cross sections below 275 eV. Recent values of the Pu-239 resonance parameters were used in the calculations.*

Table I.B.2 gives the results of the calculations.

* Schmidt, J. J., KFK-120 (1966); Durston, C., and Katsuragi, S., JAERI-1162 (1968); Fischer, E. A., KFK-844 (1969).

TABLE I.B.2. Pu-239 Doppler Effect
($\times 10^{-5} dk/kdT$)

Configuration	Doppler Effect
Plates together-- Depleted-U reflector	-0.91
Plates together-- Pb reflector	-1.5
Plates separate-- Depleted-U reflector	-0.88
Plates separate-- Pb reflector	-1.4

(ii) Supplementary Analytical
Interpretation of Integral
Data

Not previously reported.

(a) Analysis of Graphite
Density Reactivity Measurements in
ZPR-3 Assembly 53. ZPR-3 Assem-
bly 53 was the fourth in a benchmark
series of clean criticals designed for
basic physics studies of dilute pluto-
nium systems. Details of the assem-
bly composition and the experiments
were described in Progress Report

for September 1968, ANL-7500, p. 17. Although no sodium was used in
Assembly 53, experiments akin to the coolant-void coefficient were per-
formed by reducing the density of graphite in various core zones without
creating gross streaming effects through voids. Since the principal mecha-
nism in the spectral component of the sodium-void coefficient is the energy
dependence of α for the fissile isotopes, the removal of scattering material
having well-known and simple cross sections is a useful and relevant
experiment.

A 24-group cross-section set was prepared by MC²
from the ENDF/B data file, allowing for the different resonance self-
shielding conditions for each of the fuel plates. Heterogeneity calculations
were then performed for the cell to obtain the equivalent homogeneous-core
cross sections. The one-dimensional transport code TESS with its homoge-
nization routines was used for that stage of the analysis.

The flux-weighted, cell-averaged cross sections from
TESS for the high- and low-density graphite zones were used in the DIFF-2D
program.* The worths of central and axial zone replacements were calcu-
lated by k calculation differences and by various perturbation approxima-
tions using the PERC code. The results are shown in Table I.B.3.

It can be seen that the worth of graphite at the central
zone is overestimated by 50%, reflecting uncertainty in the spectral compo-
nents. The use of the more exact δD gave significant improvement in the
axial zone calculation as would be expected. Transport calculations are
being performed, since diffusion theory in this small core would signifi-
cantly overestimate the leakage term in the axial zone. Exact perturbation
theory gave further improvement over first-order theory. The two-k cal-
culation method was in good agreement with exact perturbation theory, thus
allowing the more economical perturbation calculations to be used in the
continuing analysis.

*Leaf, G. K., and Kennedy, A. S., DIFF-2D--A Two-dimensional Diffusion Theory Code, p. 104, ANL-7332;
PERC--A Two-dimensional Perturbation Code Based on Diffusion Theory, p. 151, ANL-7332.

TABLE I.B.3. Comparison between Calculations and Experimental Results for ZPR-3 Assembly 53 ($10^{-5} \Delta k/k'$)

Region	Method	Leakage	Absorption	Fission	Moderation	Total Calculation	C/E
<u>Center</u>	1st Order, $\delta D = \frac{\delta \Sigma_{tr}}{3\Sigma_{tr}^2}$	-35.6	22.3	-46.6	-200.2	-259.7	1.48
	1st Order, $\delta D = \frac{\delta \Sigma_{tr}}{3\Sigma_{tr}\Sigma_{tr}^2}$	-32.7	22.4	-46.6	-199.7	-256.6	1.46
	Exact, Perturbed Flux	-30.0	22.6	-46.8	-195.3	-249.3	1.42
	Exact, Perturbed Adjoint	-29.6	21.0	-46.2	-195.2	-249.3	1.42
	k-calculations	-	-	-	-	-253.4	1.44
<u>Axial Edge</u>	1st Order, $\delta D = \frac{\delta \Sigma_{tr}}{3\Sigma_{tr}^2}$	-59.8	2.46	-5.4	-8.4	-71.1	1.58
	1st Order, $\delta D = \frac{\delta \Sigma_{tr}}{3\Sigma_{tr}\Sigma_{tr}^2}$	-54.8	2.46	-5.4	-8.4	-66.2	1.47
	Exact, Perturbed Flux	-52.1	2.35	-5.4	-7.5	-62.6	1.39
	Exact, Perturbed Adjoint	-51.9	2.46	-5.4	-7.8	-62.6	1.39
	k-calculations	-	-	-	-	-66.8	1.49

The shape of the adjoint-flux spectrum is determined predominantly by the energy dependence of the alpha of core composition. Since the U/Pu ratio in this assembly is only 1.6, the Pu-239 α dominates. The most important cross-section uncertainty in the existing ENDF/B data file is in the Pu-239 alpha value below 25 keV; the recent measurements of Gwin *et al.*,* substantiate this conclusion. The cross-section uncertainty is all the more important for the present case, since a third of the real flux is below 25 keV. Modifications to the 24-group cross-section set are being made to incorporate Gwin's Pu-239 alpha values. Qualitatively this should result in a reduction of the magnitude of the fission and moderation terms, and an increase in the absorption term, all of which are in the direction of better agreement with experiment.

(iii) Development of ZPR Heterogeneity Analysis Methods

Last Reported: ANL-7577, p. 11 (April-May 1969).

(a) GEDANKEN Studies. The effect of heterogeneity in the plate-type ANL fast criticals is a complex problem for which only approximate methods of solution are available. Comparison of measured and calculated quantities do not offer conclusive tests of such methods due either to uncertainties in cross-section data and/or to the interacting effect of several mechanisms. One approach to the problem of testing the methods is to calculate the results of theoretical experiments that are complex enough to exhibit significant heterogeneity effects but which are simple enough to be calculated exactly by available techniques. A series of theoretical experiments called GEDANKEN cores are being analyzed to test the various

* Gwin, R., *et al.*, Measurement of Neutron Fission and Absorption Cross Sections of Pu-239, Trans. Am. Nucl. Soc. 12, 260 (1969).

methods of calculating that component of the heterogeneity effect which we call the "flux advantage factor" and to ascertain its effect on the various measurements such as critical mass, coolant voiding coefficients, central reactivity worths, and zoned experiments.

The first core, called GEDANKEN-1, is an eleven-unit-cell-wide, infinite slab core reflected on both sides by a 20-cm U-238 blanket. Each unit cell consists of a central Pu-U fuel plate ($U/Pu = 3.67$) of 0.5-cm thickness, two 1.0-cm plates of sodium, and then two 0.5-cm plates of graphite (C, Na, U-Pu, Na, C). For simplicity, no cladding, drawers, or matrix tubes are used.

Two 12-group cross-section sets were prepared by use of the MC² code; one set assumed isotropic scattering, and the other used the anisotropic option allowing P1 downscattering. The exact k of the system was found by high-order double- S_N calculations using the TESS 1D transport code. A small extrapolation of angular-mesh and linear-mesh sensitivity studies gave "exact" k 's of 1.003690 and 0.999114 for the isotropic and anisotropic sets, respectively. Similar calculations for the homogeneous (volume-weighted) core gave k 's of 0.997320 and 0.992544, yielding "exact" heterogeneity factors of 0.637% and 0.657% $\Delta k/k$, respectively. Thus the effect of anisotropy on the flux advantage factor in GEDANKEN-1 appears to be small.

Since the structure of the plate-type cores is too complex to be described directly by neutronic codes, the current approach is to transform the multiregion heterogeneous core into its equivalent "homogeneous" form to allow its treatment by conventional few-region neutronic codes. This is usually done by calculating the fine neutronic distribution across an appropriate cell and using that distribution to homogenize spatially the cross sections by some appropriate recipe. Generally two basic recipes are considered: bivariate real-adjoint weighting and real-flux weighting only. Some preliminary results are available for the real-flux weighting method applied to the GEDANKEN-1 core. The existing bivariate homogenization routine in TESS is now known to be grossly overapproximate and is presently being replaced by one based on the treatment reported in the Progress Report for February 1969, ANL-7553, p. 7.

The existing TESS homogenization routine for the real weighting considers only the scalar fluxes, whereas the real weighted equivalent of the normalization integral derived in ANL-7553 requires a $|\mu|$ weighting. These two methods were compared in the GEDANKEN-1 studies. A double- S_{20} calculation was performed across a repeating cell with a pseudo-absorption cross section $D_g B_g^2$ for each group to account for leakage.

The heterogeneity factor predicted by the $|\mu|$ weighted method was found to be 0.614%, whereas that using the scalar fluxes was

0.737%. These numbers have to be compared with the "exact" value of 0.637%. To preclude the possibility of the approximation leakage treatment affecting the result, the methods are being compared by homogenizing over each of the cells in the core using the flux distributions from the exact full-core calculations. The homogenized cross sections will then be used in six zone (half-core) calculations, the comparison of which should be a more definitive test of the two recipes.

The GEDANKEN-1 studies have also been used to test the perturbation technique for evaluating the flux advantage factor. Here the CALHET code* developed from the collision probability formulation of F. Storrer et al.,** was used. Treatment of the leakage was improved by reducing the collision probabilities by a nonleakage factor in both the homogeneous and heterogeneous arrays rather than using equivalent absorption cross sections (DB^2) in calculating the optical thickness of the plates. This modification resulted in an improvement from a $\Delta k/k$ of 0.985% to 0.665%, compared to the "exact" value of 0.637%.

(b) Statistically Generated Resonance Parameters for Pu-239. RANDOM, a code which generates reduced neutron widths from a chi-squared distribution with one degree of freedom, has been modified in order to obtain resonance parameters for Pu-239. The five sequences in the Pu-239 resonance structure correspond to the possible values of the nuclear spin J of the compound nucleus, for incident neutrons with $\ell = 0$ and $\ell = 1$. The spacing between resonances follows the Wigner distribution:†

$$P_W(X) dX = \frac{\pi}{2} X e^{-\pi/4 X^2} dX, \quad (1)$$

where $X = D/\langle D \rangle$ and D is the level spacing. The fission and reduced neutron widths follow a chi-squared distribution:†

$$P_\nu(z) dz = \frac{\nu}{2\Gamma(\nu/2)} [\nu/2z]^{\frac{1}{2}\nu-1} e^{-\nu/2z} dz, \quad (2)$$

where $z = \Gamma_y/\langle \Gamma_y \rangle$ and Γ_y is the fission or reduced neutron width, ν the number of degrees of freedom, and $\Gamma(\nu/2)$ the gamma function.

Table I.B.4 lists the number of degrees of freedom for each of the fission and neutron width distributions in the Pu-239 sequences.

*Fillmore, F. L., and Felten, L. D., The CALHET Heterogeneous Perturbation Theory Code and Application to ZPR-3--48, Atomics International AI-67-91 (Aug 1967).

**Storrer, F., et al., Heterogeneity Calculation for Fast Reactors by a Perturbation Method, Nucl. Sci. Eng. 24, 153 (1966).

†Schmidt, J. J., KFK-120.

It was necessary to distribute the level spacings statistically so that there would be no correlated overlapping effect between sequences with the same average level spacing. It has been shown* that to a first approximation there is no statistical overlap influence between resonances of different sequences.

TABLE I.B.4. Degrees of Freedom for
Chi-squared Distributions of Pu-239
Resonance Parameters

Sequence	ℓ	J	Reduced Neutron Width	Fission Width
1	0	0	1	2
2	0	1	1	1
3	1	0	1	1
4	1	1	2	1
5	1	2	1	1

c. Fast Critical Experiments--Theoretical Support--Illinois

(i) Supplementary Analytical Interpretation of Integral Data

Not previously reported.

(a) Fast Reactor Integral Studies of Modifications to ENDF/B U-238 Inelastic Scattering. A large number of calculations of fast reactor integral parameters have been carried out as part of a program of ENDF/B cross-section testing. Comparisons of these calculations with measurements have suggested the possibility that one of the chief sources of disagreement may be the errors in the U-238 inelastic scattering.

Figure I.B.4 shows k_{eff} values for fifteen critical assemblies. In most cases the homogeneous, spherical models used for

Fig. I.B.4

Calculated k_{eff} as a Function of Relative
 ^{238}U Concentration in the Core

G = Godiva
J = Jezebel
2, 3 = Zebra
1B, 11A = Vera
6F, 11, 12, 25, 32, 48 = ZPR-3
5, 6 = ZPR-6
24 = ZPR-9 $k_{\infty} = 1$ Cell

*Nicholson, R. B., and Fischer, F. A., "Doppler Effect in Fast Reactors" in Advances in Nuclear Science and Technology.

the transport calculations, as well as the experimental values, were those recommended by Davey and Hess.* A dependence of the error on the amount of U-238 present is apparent and is represented by the solid, sloping line. Other investigations,** such as the U-238/U-235 fission ratio comparisons given in Fig. I.B.5 have shown that most of the discrepancies found could be explained by consistently soft calculated spectra. For these reasons the effect of changing the U-238 $\sigma_{n'}$ was examined.

Fig. I.B.5

Comparison of Calculated and Experimental Central $^{238}\text{U}/^{235}\text{U}$ Fission Ratios as a Function of Relative ^{238}U Concentration in the Core. (See legend for Fig. I.B.4.)

Figures I.B.4 and I.B.5 are representative of the parameter changes found when the U-238 $\sigma_{n'}$ was lowered by 30%. For this magnitude of change it was found that for both k_{eff} and the U-238/U-235 fission ratios the U-238 dependence was basically removed, but the values were overcorrected in most cases. If, additionally, the U-235 σ_f above 2 MeV is lowered (as suggested by Davey[†]), much better agreement is obtained.

As a test of a more realistic change to the ENDF/B U-238 $\sigma_{n'}$, calculations were performed using the U-238 $\sigma_{n'}$ level structure of Smith^{††} as used in Argonne Set 224.[‡] This cross section essentially reduces the contribution of some of the higher inelastic levels and results in a reduction in the total $\sigma_{n'}$ of about 15% only between 1 and 2 MeV. It was found that this correction did not sufficiently increase the calculated integral values.

As a result of this work it appears that a theoretical and experimental examination of the U-238 inelastic cross section is necessary. Such work is now in progress at Argonne.

* Davey, W. G., and Hess, A. L., "Additional Fast Reactor Benchmarks for Phase II Testing of ENDF/B," CSEWG Newsletter 18, Cross Section Evaluation Working Group (March 1969).

** Kallfelz, J. M., Poenitz, W. P., Sehgal, B. R., and Zolotar, B. A., Studies of Fast Neutron Cross Sections through Integral Experiments, Trans. Am. Nucl. Soc. 12(1), 186 (1969).

† Davey, W. G., Selected Fission Cross Sections for Th-232, U-233, U-234, U-235, U-236, Np-237, U-238, Pu-239, Pu-240, Pu-241, and Pu-242, Nucl. Soc. Eng. 32(1), 35 (1968).

†† Smith, A. B., Scattering of Fast Neutrons from Natural Uranium, Nucl. Phys. 47, 633 (1963).

‡ O'Shea, D. M., et al., Twenty-six-group Cross Sections, Trans. Am. Nucl. Soc. 7(2), 242 (1964).

(ii) Development of ZPR Heterogeneity Method (C. E. Till)

Not previously reported.

(a) Plans for an ARC System ZPR Heterogeneity Package.

A series of ARC modules* are under development in an attempt to provide a convenient and reliable method for obtaining group cross sections for use in the analysis of ZPR lattices. The generation of these cross sections will include both spectral and spatial cell weighting with approximations to the heterogeneous effects included in the calculation. For the first version of this heterogeneity package the following procedure has been adopted:

1. A modified version of the MC²** code will be used to generate broad-group cross sections for each lattice plate. The assumption is made that except in the resonance range these plate cross sections are identical to those for a homogeneous cell of the same average composition. In the resolved and unresolved resonance region the capture and fission cross sections are shielded using equivalence theory on an ultrafine group basis. The two-sided E₃ formulation of Meneghetti[†] is used to find the Dancoff corrected potential cross section for each individual absorber plate. Problems relating to the proper treatment of interacting resonances in different plates are still under study.

2. In order to determine cell-averaged cross sections, the plate cross sections will be used with the ARC 1-D transport modules to obtain fluxes within the unit cell. These calculations will be made with a high-order modified single Gaussian angular quadrature.^{††} If desired, a group-dependent leakage term will be included to simulate the overall leakage from the core.

3. The broad-group flux shapes in the cell will be used to obtain homogenized cross sections appropriate for overall reactor studies.

Upon completion, this heterogeneity package will be extensively used as part of a study to test many of the assumptions inherent in such a calculation. Alternatives to the standard formulations will be examined and comparisons will be made with results from integral transport codes such as RABBLE[‡] and RABID.^{‡‡}

*Toppel, B. J., The Argonne Reactor Computation (ARC) System, ANL-7332 (1967).

**Toppel, B. J., Rago, A. L., and O'Shea, D. M., MC²--A Code to Calculate Multigroup Cross Sections, ANL-7318 (1967).

†Meneghetti, D., "Calculational Studies of Sodium-void Reactivity Variations due to Thin Slab Heterogeneities in Fast Critical Assemblies," Proc. of the Intern. Conf. on Fast Critical Experiments and Their Analysis, October 10-13, 1966, ANL-7320, pp. 377-386.

††Meneghetti, Discrete Ordinate Quadratures for Thin Slab Cells, Nucl. Sci. Eng. 4(3), 295 (1962).

‡Kier, P. H., and Robba, A. A., RABBLE, A Program for Computation of Resonance Absorption in Multi-region Reactor Cells, ANL-7326 (1967).

‡‡Olson, A. P., Resonance Absorption in Multiplate Reactor Cells by Integral Transport Theory, Trans. Am. Nucl. Soc. 11(1), 301 (1968).

2. Experimental Reactor Physics

a. Fast Critical Experiments--Experimental Support--Illinois

(i) Development of Experimental Techniques (R. Gold)

Last Reported: ANL-7577, p. 13 (April-May 1969).

(a) Automatic Testing of Analog-Digital Converters.

It is convenient to use a digital computer for automatic testing of analog-digital converters and plotting of linearity curves.* The central task in such an undertaking is the generation of highly accurate test signals. This has been done by use of resistive-network digital-to-analog converters.** To be useful, such converters must be built of very high-quality, expensive components. Otherwise, they exhibit serious nonlinearities where the higher-order bits change state.

Accurate test signals can be generated much more easily by suitable modification of a commercial voltage-to-frequency converter. Such an instrument integrates its input signal in an analog integrator. When the integrator output reaches a certain level, an accurately standardized pulse is transmitted to the integrator input. This pulse removes charge from the integrator, beginning a new cycle. A corresponding output pulse is also generated.

For the modification, the input of the standardized-pulse generator is disconnected from the analog integrator and is, instead, triggered on command from the computer. Thus, each command adds a standardized charge to the integrator, producing a step in the integrator output. With all steps identical, the differential linearity of this arrangement is extremely good throughout its range.

A relay is installed which can be actuated under computer control to short the integrating capacitor[†] and so reset the test signal to zero. On the voltage-to-frequency converter used here (Vidar 241), the operational amplifier could not handle the desired 10-V output range. Therefore, an additional operational amplifier was installed to boost the output to the desired range and provide test signals of either polarity. The integrating capacitor was increased from 330 pF to 5 μ F, giving a range of 4096 steps.

*Cohn, C. E., Automatic Testing of Analog-Digital Converters, Trans. Am. Nucl. Soc. 12(1), 313 (June 1969).

**Gardner, F. M., and McKeethen, R., Digital-to-Analog Pulser System for Testing Pulse-height Analyzers, Nucl. Instr. Methods 46, 121 (1967); Greenblatt, J., Kuchela, K. S., and Sherman, N. K., A Digitally Controlled Precision Pulser, *ibid.*, 49, 86 (1967); Lycklama, H., and Kennett, T. J., A Linearity Measurement Technique for Analogue-to-Digital Converters, *ibid.*, 59, 56 (1968).

[†]Wadsworth, B. F., "Two Relay Contacts Clear Integrator for Rapid Operation," 100 Ideas for Design No. 1, p. 24, Hayden Book Co., New York (1961).

To test an ADC, the test signal is reset and then stepped through its range. At each level the response of the ADC is observed. The responses are fit to a straight line and the residuals are plotted. If the ADC is a pulse type, the test voltage is applied to a mercury-switch pulser.

The fits may also be used to facilitate adjustment of the ADC offset level. Tests are made for two settings of the ADC offset dial. The computer then extrapolates to an offset that would give a fitted line with an intercept of zero channels. The dial is manually set to the calculated offset, and another test is made. The process is repeated until the intercept is zero to the desired accuracy. Ordinarily, only one or two iterations are needed. Alternatively, the offset need not be adjusted, but the computer can use the fitted intercept to adjust pulse-height data as they are received.

b. FFTF Critical Assembly Experiments--Planning and Evaluation
(A. Travelli)

Last Reported: ANL-7595, pp. 14-16 (July 1969).

(i) Calculation of Reaction-rate Traverses in ZPPR/FTR-2.
The radial variations of ^{239}Pu fission and ^{10}B capture detector responses in ZPPR/FTR-2 have been calculated. The flux distribution was obtained using the 29-group cross-section set (29004,2) (see Progress Report for March 1969, ANL-7561, p. 7) in one-dimensional cylindrical-transport theory in the S-4 approximation. The SNARG-1D code* was used in the calculations with the transport approximation for the anisotropic scattering.

The axial leakage was simulated by a DB^2 absorber. The transverse buckling ($6.260 \times 10^{-4} \text{ cm}^{-2}$) was obtained through a series of cylindrical and slab calculations converging by iteration to a pair of calculations corresponding to the same k and to transverse bucklings up to the material buckling ($1.778 \times 10^{-3} \text{ cm}^{-2}$). The dimensions and material compositions of the cylindricized reactor are given in ANL-7595 and in Progress Report for April-May 1969, ANL-7577, p. 42. The value of k obtained through this procedure was 0.984.

Two reaction-rate traverses were computed for each of the three detector types from the neutron-flux distribution. In the calculation of the first reaction-rate traverse the 29-group cross sections obtained from a 2,100 group fundamental mode MC^{2**} flux averaging for the core composition at criticality were used. The flux was normalized so that the reaction rate obtained in this calculation was unity at the core center. In the calculation of the second reaction-rate traverse the 29-group cross

*Duffy, G. J., et al., ANL-7221 (1966).

**Toppel, B. J., et al., ANL-7318 (1967).

sections obtained from a 2,100 fundamental mode MC^2 flux averaging for the reflector composition with zero buckling were used. The same flux, with the same normalization, was used as in the calculation of the first reaction-rate traverse.

The computed responses for the three types of detectors are compared in Fig. I.B.6 with the experimental values. The experimental data are indicated by crosses, the reaction rates obtained in the first calculation (core spectrum averaging) are indicated by the dotted curves labeled "1," and the reaction rates obtained in the second calculation (reflector spectrum averaging) are indicated by the dotted curves labeled "2." Thus, type-1 curves are valid close to the core center, and type-2 curves are valid in the regions well inside the reflector.

Comparison of the ^{239}Pu and ^{10}B radial detector response curves in Fig. I.B.6 with the analogous curves for ZPR-3 Assembly 56B in Fig. I.B.7 show the depressing effect of the B_4C control ring on the ^{239}Pu and ^{10}B reaction rates, not only in the reflector, but also in the outer 20-30 cm of the core. Agreement between calculated and measured responses for ZPPR/FTR-2 is within 10% for ^{239}Pu and ^{10}B , except near the outer edge of the radial reflector of ZPPR/FTR-2. The computation of the detector response curves for Assembly 56B is described in Progress Report for April-May 1969, ANL-7577, p. 15 (in ANL-7577 the caption for Fig. I.B.2 should read "Axial Reaction-rate Traverses in ZPR-3 Assembly 56B.")

Fig. I.B.6. Radial Reaction-rate Traverses in ZPPR/FTR-2

Fig. I.B.7. Radial Reaction-rate Traverses in ZPR-3 Assembly 56B

The calculated curves were based on a solution which assumed simply that the outer edge of the radial reflector was bare, thus causing the calculated detector responses to approach zero rapidly at that boundary. Actually, backscattering of neutrons by the stainless steel matrix structure outside the reflector occurred. This effect is apparent in the calculated detector responses for ZPPR/FTR-2, which are low near the outer edge of the reflector for ^{239}Pu fission and ^{10}B capture, both of which are more sensitive to the neutron spectrum in the reflector than is the ^{238}U fission. The contribution of backscattering by the matrix is almost negligible in the radial detection responses for Assembly 56B, where there was no B_4C control ring.

The measured ^{238}U fission response in ZPPR/FTR-2 showed little change in shape from that of Assembly 56B due to the B_4C control ring. On the other hand, the calculated ^{238}U fission response in ZPPR/FTR-2 is too small in the B_4C control ring and in the outer 20-30 cm of the core. These are the regions where the control ring caused a pronounced depression in the ^{239}Pu fission and ^{10}B capture, both measured and calculated. This discrepancy warrants further investigation.

3. ZPR-6 and -9 Operations and Analysis

a. Zoned Critical Experiments (L. G. LeSage)

Not previously reported.

(i) ZPR-9 Assemblies 25 and 25A. Assemblies 25 and 25A of ZPR-9 have been designed. Assembly 25, which will be constructed first is a small, uranium-loaded, zoned critical assembly with a central test zone designed to have a k_∞ of unity. Assembly 25 is cylindrical, and consists of a central test zone surrounded by concentric buffer, driver, and reflector region. The test zone is composed primarily of enriched and depleted uranium, and has a hard energy spectrum, with very few neutrons in the resonance energy region. Assembly 25A is similar to Assembly 25 except that the central test zone will be composed of plutonium (ZPR-3-type metal plates) and depleted uranium. The average homogeneous atomic concentrations and the predicted region sizes are given in Table I.B.5. The volume percentages for the materials in each region are given in Table I.B.6,

TABLE I.B.5. Atomic Concentrations and Dimensions for ZPR-9 Assemblies 25 and 25A

	Atomic Densities ($\times 10^{21}$)										Outer Radius (cm)	Total Drawer Req.
	^{239}Pu	^{240}Pu	^{241}Pu	^{235}U	^{238}U	C	Fe	Ni	Cr	Al	Mo	
Core ^a Assembly 25	-	-	-	2.1700	28.489	-	6.8385	0.8643	1.9518	4.0389	-	74
Core ^a Assembly 25A	1.6134	0.0766	0.00743	0.0623	33.712	-	8.0672	1.0192	2.3028	1.5136	-	-
Buffer	-	-	-	0.07265	33.973	-	6.8385	0.8643	1.9518	6.2521	-	64
Driver	-	-	-	4.5531	0.32487	51.996	13.043	1.6483	3.7223	-	-	154
SS Reflector	-	-	-	-	-	-	56.472	7.1363	16.115	-	-	372
Depleted-uranium Reflector	-	-	-	0.081	39.93	-	4.332	0.54	1.14	-	-	404

^aThe atomic concentration of ^{238}U in the core region has been changed slightly to adjust $k_\infty = 1$ for this region.

TABLE I.B.6 Volume Percentages for ZPR-9 Assemblies 25 and 25A

Region	Volume Percent						
	Pu	Enriched Uranium	Depleted Uranium	Al	C	SS	Air (Void)
Core Assembly 25	-	5.3	63.5	7.1	-	11.4	12.6
Core Assembly 25A	3.5	-	71.5	2.7	-	13.4	8.9
Buffer	-	-	74.1	10.6	-	11.4	3.9
Driver	-	10.6	-	-	63.5	22.0	3.9

and the initial drawer loading arrangements are shown in Fig. I.B.8. The calculated multigroup central spectra for both assemblies are shown in Fig. I.B.9. The calculated spectrum for a previous null (i.e., $k_{\infty} = 1$) zoned assembly, ZPR-3 Assembly 55, is shown for comparison. Assembly 55 was designed to have a soft spectrum for low-energy measurements of plutonium alpha.

The measurements planned for Assemblies 25 and 25A are aimed at providing integral data relevant to the resolution of some of the cross-section uncertainties in the fertile and fissile isotopes, primarily ^{238}U and ^{239}Pu .

Fig. I.B.8. Drawer-loading Patterns for ZPR-9 Assemblies 25 and 25A

Fig. I.B.9. Calculated Central Null-zone Spectra for Assemblies 25 and 25A of ZPR-9 and Assembly 55 of ZPR-3

b. Doppler Experiments (J. W. Daughtry and R. B. Pond)

Last Reported: ANL-7548, pp. 23-26 (Jan 1969).

(i) Doppler Effect Measurements in ZPR-6 and -9 Oxide Cores.

Measurements of the Doppler effect for uranium were made at the center of ZPR-6 Assembly 6 and in two smaller zoned assemblies, ZPR-9 Assemblies 19 and 21. The core of ZPR-6 Assembly 6 was built with ^{235}U fuel, and was similar in composition, size and spectrum to oxide-fueled LMFBR designs. The central cores of the zoned assemblies had the same composition as Assembly 6, but were surrounded by an enriched driver region and a buffer region designed to achieve criticality at a relatively low critical mass, and to produce real and adjoint centerline fluxes as similar as possible to those of the full-size Assembly 6. The central core volumes of Assemblies 19 and 21 were 192 and 58 liters, respectively, compared to about 4000 liters for Assembly 6.

The results of the Doppler measurements are summarized in Table I.B.7. An oscillation technique* was used to measure the reactivity changes due to heating the small uranium samples. For these experiments the samples were natural and enriched UO_2 , 1 in. in diameter by 12 in. long, each containing about 1 kg of uranium. A detailed study (see Progress Report for July 1968, ANL-7478, p. 16) of the effect of the immediate environment around the sample on the measured Doppler effect has led to the adoption of a standard configuration for most Doppler measurements made in ZPR-6 and -9. The purpose of this standard configuration is to reduce the hot-cold resonance-interaction effect. The reduction is achieved by introducing a stainless steel filter between the Doppler sample and the

*Reactor Physics Division Annual Report: July 1, 1965 to June 30, 1966, ANL-7210, pp. 129-137.

reactor core. In the standard environment a total of 1/2 in. of stainless steel separates the sample material from the core materials. This configuration was used for the measurements reported here except for the one case indicated in Table I.B.7 in which a 3/4-in.-thick filter was used.

TABLE I.B.7. Doppler Measurements in ZPR-6 Assembly 6 and ZPR-9 Assemblies 19 and 21

Assembly	Sample Temperature (°K) ^a Reactivity Change [Ih/(kg-U)] ^b				Comments
	Natural Uranium				
ZPR-6	505	811	1081		
Assembly 6	-0.132	-0.266	-0.353		
ZPR-9	800	1055			
Assembly 19	-0.497	-0.628			
ZPR-9	776	1041			
Assembly 21	-0.594	-0.795			
Enriched Uranium ^c					
ZPR-6	759	764	1023	1041	
Assembly 6	+0.056	+0.050	+0.059	+0.055	
ZPR-6	509	768	1042		3/4-in. Stainless Steel Filter
Assembly 6	+0.041	+0.061	+0.075		
ZPR-6	406	642	826	1030	Expansion Constrained
Assembly 6	+0.019	+0.041	+0.047	+0.058	
ZPR-9	765	1048			
Assembly 21	+0.111	+0.114			

^aData normalized to 0.000 Ih/(kg-U) at 293°K and uncorrected for expansion.

^bRoot-mean-square error $\sigma \approx 0.002$ Ih/(kg-U).

^c97.7% ²³⁵U.

The reactivity effect due to expansion has been found to be negligible for the natural uranium samples. This is, however, not the case for the enriched samples, in which the Doppler effect itself is much smaller. In these experiments, one set of data was obtained with a sample having constrained expansion characteristics. The remainder of the data was obtained with freely expanding samples. The constrained expansion was achieved by a special capsule design* that permits no sample expansion from room temperature to about 200°C and radial, but not axial, expansion above 200°C. None of the data of Table I.B.7 has been adjusted for expansion effects.

The root-mean-square error σ in Table I.B.7 applies to the normalization point of 0.000 Ih/(kg-U) at 293°K as well as to the data points at higher temperature.

*Till, C. E., Groh, E. F., and Lewis, R. A., Equipment and Techniques for Doppler-effect Measurements on Fast Critical Assemblies, Trans. Am. Nucl. Soc. 8, 455-456 (Nov 1965).

(ii) Installation of Doppler Equipment in ZPR-6. During the modifications of the ZPR-6 facility for plutonium conversion, all the equipment and associated electrical wiring for making Doppler-effect measurements was removed from the ZPR-6 cell and control room. Much of the equipment was modified to make the experiments more precise and routine and has been reinstalled. The Doppler oscillator is now driven by an air motor which holds the oscillator firmly against positive stops for the sample-in and sample-out conditions, providing very accurate reproducibility of position. The cooling air system that prevents heat transfer from the Doppler sample to the reactor core had previously been controlled at the air source in the basement. Air-flow controls and flow-rate meters are being installed in the ZPR-6 and -9 control rooms to permit continuous monitoring and control by the experimenter. The coarse and fine autorods remain to be installed.

The Doppler equipment is to be used in ZPR-6 Assembly 6A for measurements of the ^{238}U and ^{235}U Doppler effect in a large sodium voided zone.

c. Heterogeneity Measurements (R. A. Karam and R. A. Lewis)

Last Reported: ANL-7527, pp. 13-22 (Dec 1968).

(i) Sensitivity of Critical Mass to the Treatment of Heterogeneity Effects in a Large UC Fast Core, Assembly 5 of ZPR-6. Two main types of heterogeneity effects are associated with fast criticals loaded in plate geometry: fast and resonance. The fast effect depends on the physical shape of the fissile materials, i.e., thicknesses and lengths of columns, and on the physical separation between the fissile and fertile plates. Increasing heterogeneity gives a positive contribution to the reactivity of the system.

Resonance neutrons are readily absorbed at the plate surface, resulting in fewer such neutrons reaching the plate interior and thus lowering the average reaction rates. Resonance self-shielding contributes negatively through the fission and positively through the capture processes. It contributes either positively or negatively through scattering events; the sign is determined by the relative importance of the neutron before and after scattering.

The critical mass of Assembly 5 of ZPR-6* was calculated with various cross-section sets (25 groups) generated from ENDF/B data to evaluate the magnitude of the various types of heterogeneity effects. The cross-section sets were used with one- and two-dimensional diffusion codes and with one-dimensional transport code. The results along with descriptions of the various sets are listed in Table I.B.8.

*Karam, R. A., et al., Reactor Physics Division Annual Report, ANL-7310 (1968), pp. 167-189.

TABLE I.B.8. Calculated Critical Mass of Assembly 5 of ZPR-6

Cross-section Set	Code	Critical Mass (kg ^{235}U)	k_{eff} for As-built ^a System	Remarks
Set A	1-D Diff.	2326	0.976196	Set A generated with MC ² code from ENDF/B data for homogeneous composition of Assembly 5.
Set B	1-D Diff.	2147	0.980954	^{238}U resonance-region cross sections in Set A corrected for spatial self-shielding via equivalence theory.
Set C	1-D Diff.	2026	0.985200	Cross sections in Set B spatially averaged with one-dimensional fine structure of real flux in unit cell.
Set D	1-D Diff.	2038	-	Cross sections in Set B spatially averaged with two-dimensional fine structure of real flux.
Set E	1-D Diff.	1922	-	Cross sections in Set B bilinearly averaged with real and adjoint fluxes obtained from one-dimensional transport calculation.
Set C	2-D Diff.	1981	-	Two-dimensional diffusion calculation using Set C.
Set C	1-D Trans.	1859	-	One-dimensional transport calculation.
Set C	1-D Trans.	1755	0.990948	One-dimensional transport calculation using measured extrapolated axial height.

The Measured Critical Mass was 1585 kg of ^{235}U .

^aThe k_{eff} calculations were done with the measured extrapolated height of 180.0 cm. Unless otherwise indicated a calculated extrapolated height of 171.4 cm was used in all calculations.

These results show that the equivalence-theory correction for spatial self-shielding in ^{238}U resonances decreases the true homogeneous critical mass by 7.7% and increases k_{eff} by 0.47%. Weighting Set B with the one-dimensional fine structure of the real flux in the unit cell decreases the critical mass by 5.6% and increases k_{eff} by 0.43%. Bilinear weighting of Set B with the spatial distribution of the real and adjoint fluxes reduced the critical mass by another 5%. Spatial averaging with two-dimensional unit-cell fine structure of the real flux yields similar results to one-dimensional spatial averaging, indicating that the isotropic leakage assumption made in the one-dimensional cell calculations is adequate. The difference between transport- and diffusion-theory calculations is about 0.6% in k_{eff} . The lowest calculated critical mass (1775 kg) would have been reduced further had bilinear weighting of the cross section been used in the transport calculation.

Experimental evidence* indicates that the fast heterogeneity effect as inferred from the measured spatial distribution of the ^{238}U fission

*Karam, R. A., et al., Reactor Physics Division Annual Report, ANL-7410 (1969), pp. 133-140; Karam, R. A., et al., Trans. Am. Nucl. Soc. 11, 598 (1968).

rates within the unit cell is accounted for reasonably well. However, the calculated central reactivity difference between a homogeneous sample (Set A) and a plate-type heterogeneous sample (Set C) was lower by about a factor of 4 than the experimental value. The measured reactivity worth of a nominally 2-in.-cube, plate-type heterogeneous sample was 20% more than an equivalent homogeneous sample. Both samples had the core composition of Assembly 5. It appears, therefore, that equivalence theory is not adequate for the treatment of the resonance heterogeneity effect in the complex plate geometry. Consequently, the reasonable agreement between the calculated (1755 kg) and measured (1585 kg) critical mass should not be interpreted as an indication of the accuracy of ENDF/B data and/or the validity of the methods for treating heterogeneity effects. Further refinement and validation of the calculational methods are needed.

4. ZPR-3 and ZPPR Operations and Analysis

a. Clean Critical Experiments (P. I. Amundson)

Last Reported: ANL-7595, pp. 19-20 (July 1969).

The Assembly 57 experiments and preparations for the high-power run continued. The core contains U-235, U-238, and BeO plates in a composition designed to provide measurements of the capture-to-fission ratio (α) of U-233, U-235, and Pu-239 below 25 keV.

The neutron spectrum was measured near the center of the core in Assembly 57 by means of a proton-recoil spectrometer. ZPR-3 Assembly 57 was a mockup of the STSF-1A, a subcritical assembly built at Gulf General Atomics. The region outlines and the major features of the mockup are shown in Fig. I.B.10. This loading was subcritical by approximately 7.4% $\Delta k/k$. The core contained 77.31 kg of 93.1% enriched uranium (72.02 kg U-235). The mass changes resulting from the plate substitutions described below are negligible. The geometry and composition were the same as for the Assembly 57 critical loading (see Progress Report for June 1969, ANL-7581, p. 10) with the following exceptions:

1. The size of the core was reduced to match that of the STSF-1A assembly.
2. The central core drawer in Half 1 was replaced with the drawer containing the proton-recoil counter and preamplifier. This corresponds to the location of the LINAC target in the STSF-1A assembly.
3. The re-entrant tube through which the beam of core neutrons was extracted in STSF-1A was mocked up by removing the materials normally loaded in the region from 2 to 3 in. from the midplane in Half 2.

HALF 1

B - MOCKUP OF BEAM TUBE

S - SAFETY RODS

C - CONTROL RODS

HALF 2

P - PROTON RECOIL COUNTER

T - STARTUP SOURCE TUBE

Fig. I.B.10. ZPR-3 Assembly 57

A measurement of the proton-recoil spectrum was also made during the approach-to-critical for Assembly 57. The loading differed in two respects from that for the later measurement:

1. The re-entrant tube was not simulated.
2. There were dummy-loaded core drawers (all materials loaded except for the replacement of the fuel by depleted uranium) outside the core. All drawers (except in the corners) in the central 7 x 7 array contained a core material loading. The effect was to substitute BeO for iron in two drawers in each corner of the assembly.

The subcriticality of this loading was estimated to be $5.4\% \Delta k/k$. Each of the core differences contributed about $1\% \Delta k/k$, to account for the reactivity difference from the later subcritical loading.

Experiments completed this month include:

1. the measurement of alpha by the reactivity reaction rate method;*
2. axial and radial reactivity worth traverses with the californium source at two power levels to separate the material and neutron contributions;
3. radial reaction-rate traverses of B-10, U-235, U-238, and Pu-239;
4. additional autorod calibrations and special "rod-drop" experiments designed to determine the relative contributions of fission-product delayed neutrons and delayed photoneutrons from the beryllium in the core. Early inverse kinetics analyses showed that the delayed photoneutron contribution was significant and did affect the calculated results. Consequently, no reactivity experiments can be analyzed until the delayed photoneutron analysis can be completed.

b. Mockup Critical Experiments (W. P. Keeney)

Last Reported: ANL-7595, pp. 20-26 (July 1969).

The transition experiments and the reaction-rate distributions for ZPPR Assembly 1 have been completed. ZPPR Assembly 1 is Assembly 2 of the FTR Resumed Phase-B Critical Experiments Program. At the completion of the measurements of reaction-rate distributions, the experimental program was interrupted for seal and containment tests of the ZPPR containment system.

*Redman, W. C., and Bretscher, M. M., Nucl. Sc. Eng. 27, 34 (1967).

(i) Calibrations of Control and Safety Rods. The control and safety rods of the FTR-2 assembly were calibrated using the inverse kinetics method. First, the effective neutron source of the system was determined from the power history resulting from three 100-sec reactor periods initiated from a power level of approximately 5 W. Then, from a stabilized power level of about 100 W, each rod being calibrated was individually driven from its most reactive position to its least reactive position and the flux history recorded. The rod worths were then determined from analyses of the flux history by means of the measured neutron source constant and the delayed-neutron fractions calculated for the FTR-2 assembly (see ANL-7595, p. 24). This method indicated the total worths of the 20 safety rods and of the six control rods as $2.4\% \Delta k/k$ and $0.9\% \Delta k/k$, respectively.

As reported in ANL-7595, the ZPPR/FTR-2 reference loading (1-70) contains a fissile mass of 527.04 kg. This loading includes two partially withdrawn fueled control rods located at a radius of 35.1 cm, one withdrawn 10.000 in. and the other 5.004 in. By means of the information provided by the measurement of the neutron source constant and the calibration of the control rods, the excess reactivity of this reference loading was determined as 102.5 lh.

(ii) Temperature Coefficient. The temperature coefficient was measured by shutting off the reactor cooling system and allowing the reactor power level to drift for a period of 28 min while monitoring the core temperature and flux history. The core temperature was obtained by averaging the data recorded from five thermocouples located between the matrix tubes in the central region of the core. By means of the inverse kinetics technique, the flux history was analyzed to determine the associated reactivity effect. The resulting temperature coefficient was $-1.96 \text{ lh}/^\circ\text{C}$ and is used to correct measured reactivity differences for temperature effects.

(iii) Edge-worth Measurements. The edge worths of core-control ring and control ring-reflector exchanges were measured at the respective interfaces of the FTR-2 assembly to allow calculational cylindricalization of the system. The reactivity effect resulting from these exchanges was measured by determining the position of the calibrated control rods necessary to maintain a power level of 10 W. For the measurements at the core-control ring boundary the exchanges were done in such a manner that the control-ring volume remained constant, as in the ZPPR/FTR-2 Reference Loading 1-70, while the core volume changed.

Listed in Table I.B.9 are the exchanges made and the corresponding measured reactivity worths. Each worth was derived from the difference of two measurements, i.e., the difference of the 10-W control-rod position for the reference loading and for the loading containing the edge-worth exchange. Applying the temperature coefficient of $-1.96 \text{ lh}/^\circ\text{C}$, the rod

positions were temperature normalized before obtaining the reactivity difference. The uncertainty of each measurement was ± 0.41 lh, making the uncertainty of an exchange ± 0.58 lh, and was based upon the reproducibility of the 10-W control-rod position for the reference loading. This worth uncertainty of ± 0.58 lh does not include the $\sim \pm 2\%$ uncertainty in the control-rod calibration.

TABLE I.B.9. Edge-worth Measurements for ZPPR 1/FTR 2 (Loading 1-70)

Matrix Position	Radius ^{a,b} (cm)	Fissile Mass ^c (kg)	Exchanges ^d	Worth of Exchanges ^{e,f} (lh)
127-35	58.78	1.0116	C.R. for Core	-36.20
125-35	70.15	0.0	R.R. for C.R.	
134-27	57.85	1.0116	C.R. for Core	-36.28
134-25	68.46	0.0	R.R. for C.R.	
133-27	59.83	1.0116	Core for C.R.	+28.65
133-25	70.14	0.0	C.R. for R.R.	
130-29	59.86	1.0116	Core for C.R.	+27.25
129-28	67.83	0.0	C.R. for R.R.	
128-31	61.62	1.0116	Core for C.R.	+23.12
127-30	69.47	0.0	C.R. for R.R.	
128-32	58.83	0.5088	C.R. for Core	-24.06
127-31	66.56	0.0	R.R. for C.R.	
132-28	57.45	0.5088	C.R. for Core	-26.45
131-27	65.16	0.0	R.R. for C.R.	
131-28	60.56	0.5088	Core for C.R.	+15.72
130-27	68.41	0.0	C.R. for R.R.	
127-34	60.06	0.5088	Core for C.R.	+22.56
125-34	71.23	0.0	C.R. for R.R.	
130-27	68.41	0.0	C.R. for R.R.	-3.02
125-40	71.23	0.0	C.R. for R.R.	-3.90
126-42	69.24	0.0	C.R. for R.R.	-3.57
135-25	67.23	0.0	R.R. for C.R.	+4.75

^aEquivalent cylindrical core radius and outer radius of the B₄C control ring equal 59.24 and 68.75 cm, respectively.

^bRadius measured from center of core central drawer to drawer center in given matrix position.

^cPu-239 + Pu-241 + U-235.

^dC.R. for Core = Exchanged control ring materials for core materials.
R.R. for C.R. = Exchanged radial reflector materials for control ring materials, etc.

^eWorth uncertainty is ± 0.58 lh and does not include the $\pm 2\%$ uncertainty in the control-rod calibration.

^fIn the case of a dual exchange, the reported worth represents the total reactivity effect resulting from the two substitutions.

The completion of the ZPPR/FTR-2 edge-worth measurements concluded the FTR-2 transition experiments.

(iv) Radial Reaction-rate Distributions: U-238, Pu-239, and B-10. Radial reaction rates with U-238, Pu-239, and B-10 counters were made at an axial position of 3.036 in. from the reactor midplane (in Half 1). The drawer loadings through Row 137 were modified to accommodate the traverse guide tube.

A description of the BF_3 counter is given in the Progress Report for May 1968, ANL-7457. The Pu-239 and U-238 counters were the new ZPPR traverse type which are gas flow, cylindrical, with the fissionable material plated on the inside surface of the cylinder. The active length of these counters is defined by end plugs which cover the end portions of the fissile plating. Table I.B.10 describes the counters.

TABLE I.B.10. Physical Description U-238 and Pu-239 ZPPR Traverse Counters

Counter No.	Major Plating Material	Total Material Plated ^a [(μg) $\pm 1\%$]	Isotopic Analysis of Plating Material (a/o)	Cathode (Outer Wall) Material	Anode Material	Active Length
76	Pu-239	107.7	94.452% Pu-239 5.263% Pu-240 0.272% Pu-241 0.013% Pu-242	0.455-in.-OD, 304 SS tubing, 0.010-in. wall	0.040-in.-OD, SS hypodermic tubing	2.173 in.
114	U-238	1214.8	99.9986% U-238	0.455-in.-OD, 304 SS tubing, 0.010-in. wall	0.040-in.-OD, SS hypodermic tubing	2.173 in.

^aCorresponds to a plating length of 2.345 in.

These counters were moved radially through the assembly connected to a 0.375-in.-OD, Type 304 stainless steel push rod, with a 0.095-in. wall thickness which contained RG 174/U cable. An identical rod with cable occupied the guide tube on the opposite side of the counter. The traverse guide tube was a 0.5-in.-OD, 0.010-in.-wall-thickness, Type 304 stainless steel tube which extended completely through the assembly.

The reaction-rate distributions, normalized to unity at the core center, are listed in Tables I.B.11, I.B.12, and I.B.13.

TABLE I.B.11. Pu-239 Radial Traverse Data for ZPPR 1/FTR 2
(Counter 76)

Encoder Position ^a (in.)	Normalized Count Rate ^{b,c}	Encoder Position ^a (in.)	Normalized Count Rate ^{b,c}	Encoder Position ^a (in.)	Normalized Count Rate ^{b,c}
-8.692	0.857	11.952	0.745	26.076	0.109
-7.606	0.883	13.038	0.704	26.600	0.113
-6.520	0.913	14.125	0.649	27.162	0.120
-5.433	0.949	15.211	0.607	29.336	0.160
-4.346	0.960	16.298	0.560	30.423	0.166
-3.260	0.991	17.384	0.497	31.509	0.161
-1.087	1.002	18.470	0.448	32.595	0.147
00.000	1.000	19.557	0.390	33.681	0.126
1.086	0.996	20.643	0.337	34.768	0.104
2.173	0.992	21.731	0.276	36.942	0.072
3.259	0.978	22.817	0.217	39.115	0.067
4.346	0.961	23.904	0.159	00.000	0.998 ^d
5.433	0.951	24.500	0.138	00.000	1.006 ^d
6.520	0.919	24.989	0.124	6.520	0.913 ^d
7.605	0.896	24.989	0.125	00.000	1.007 ^d
8.692	0.862	25.500	0.116	00.000	0.993 ^d
9.778	0.825	25.500	0.115		
10.865	0.784	26.076	0.110		

^aAn encoder position of 00.000 corresponds to the radial center of the core.

^bThe statistical uncertainty in each normalized count rate is no greater than $\pm 1\%$ for one standard deviation.

^cThe normalized count rate is the count rate normalized to a specific power and to the count rate at the radial center of the core.

^dRepeat points, taken during traverse.

TABLE I.B.12. BF₃ Radial Traverse Data for ZPPR 1/FTR 2
(Counter RSN-210S F2201)

Encoder Position ^a (in.)	Normalized Count Rate ^{b,c}	Encoder Position ^a (in.)	Normalized Count Rate ^{b,c}	Encoder Position ^a (in.)	Normalized Count Rate ^{b,c}
-9.778	0.809	11.952	0.745	26.618	0.122
-7.606	0.876	13.038	0.694	27.162	0.149
-6.519	0.918	14.124	0.645	27.705	0.179
-5.433	0.937	15.211	0.605	28.248	0.212
-4.346	0.961	16.297	0.553	28.791	0.240
-3.259	0.984	17.383	0.493	29.336	0.262
-2.172	0.998	18.471	0.443	30.442	0.285
-1.086	1.001	19.557	0.397	31.508	0.289
00.000	1.000	20.100	0.365	32.596	0.271
1.086	1.003	20.643	0.342	33.682	0.238
2.173	0.996	21.186	0.304	34.768	0.199
2.173	0.994	21.729	0.273	35.854	0.157
3.260	0.976	22.273	0.242	36.940	0.139
4.347	0.950	22.816	0.211	38.026	0.132
5.433	0.938	23.359	0.182	39.112	0.127
6.519	0.925	23.902	0.157	40.000	0.124
7.605	0.898	24.446	0.136	00.000	1.000 ^d
8.691	0.851	24.989	0.121	00.000	1.002 ^d
9.778	0.823	25.532	0.113	00.000	0.996 ^d
10.864	0.788	26.075	0.113	00.000	0.993 ^d

^aAn encoder position of 00.000 corresponds to the radial center of the core.

^bThe statistical uncertainty in each normalized count rate is no greater than $\pm 1.0\%$ for one standard deviation.

^cThe normalized count rate is the count rate normalized to a specific power and to the count rate at the radial center of the core.

^dRepeat points, taken during traverse.

TABLE I.B.13. U-238 Radial Traverse Data for ZPPR 1/FTR 2
(Counter 114)

Encoder Position ^a (in.)	Normalized Count Rate ^{b,c}	Encoder Position ^a (in.)	Normalized Count Rate ^{b,c}	Encoder Position ^a (in.)	Normalized Count Rate ^{b,c}
-8.693	0.837	8.692	0.858	25.250	0.097
-7.588	0.865	9.761	0.821	26.076	0.076
-6.530	0.885	10.865	0.759	26.600	0.066
-5.415	0.922	11.935	0.728	27.146	0.056
-4.347	0.964	13.038	0.708	27.750	0.048
-3.259	0.952	14.108	0.643	28.250	0.042
-2.173	0.942	15.211	0.591	29.319	0.031
-1.085	0.974	16.280	0.548	30.422	0.022
00.000	1.000	17.384	0.504	31.492	0.016
1.069	0.979	18.453	0.440	32.595	0.012
2.173	0.953	19.557	0.379	33.664	0.009
2.750	0.951	20.626	0.332	34.768	0.006
3.242	0.960	21.730	0.274	00.000	0.987 ^d
4.346	0.963	22.799	0.212	00.000	0.998 ^d
5.415	0.923	23.904	0.147	00.000	0.997 ^d
6.520	0.888	24.972	0.105	00.000	1.001 ^d
7.588	0.875				

^aAn encoder position of 00.000 corresponds to the radial center of the core.

^bThe statistical uncertainty in each normalized count rate is no greater than $\pm 1\%$ for one standard deviation in core and B₄C regions and no greater than 3% in the Ni-Na reflector region.

^cThe normalized count rate is the count rate normalized to a specific power and to the count rate at the radial center of the core.

^dRepeat points, taken during traverse.

C. Component Development--LMFBR

1. Sodium Technology Development

a. On-Line Monitoring and Sampling Development for Sodium Systems

(i) Evaluation and Improvement of the Carbon Diffusion Cell (J. T. Holmes)

Not previously reported.

A United Nuclear Corporation (UNC) carbon meter is being installed in the sodium loop that is for investigating the stability of isotopic tags in circulating sodium (see Progress Report for June 1969, ANL-7581, p. 54). The loop is being modified to test on-line monitoring systems and, henceforth, will be referred to as the Test and Evaluation Apparatus (TEA).

The UNC carbon meter is to be tested and certified prior to its installation at EBR-II early in FY 1971. The tests will employ typical EBR-II operating conditions (e.g., temperature and impurity levels) as well as abnormal conditions in which significant amounts of carburizing agents are injected into the liquid sodium. A device for exposing metallurgical tabs to the sodium and for sampling the sodium is being incorporated in parallel with the UNC carbon meter. This will enable correlations to be made between response of the carbon meter, carbon content of the sodium, and rates of carburization.

The instrumentation and controls of TEA and of the carbon meter are now being installed and checked, after which the experimental program with liquid sodium will commence.

b. Fundamentals of Corrosion in Liquid Metals

(i) Corrosion Inhibition by Dissolved Getters in Liquid Sodium Environment (K. Natesan and C. A. Youngdahl)

Last Reported: ANL-7553, pp. 83-85 (Feb 1969).

An apparatus was constructed (see Fig. I.C.1) for studies of the effect of calcium dissolved in sodium on the activity of oxygen in solution in sodium. The sodium (about 2.2 liters) is contained in a high-purity molybdenum crucible. Purified helium is used as the cover gas. The oxygen activity in the liquid sodium is measured with United Nuclear oxygen-meter cells. The crucible can be moved up and down hydraulically so that the ThO_2 -15 w/o Y_2O_3 electrolyte of the cells need be in contact with the

sodium only while emf measurements are being made. This design will probably permit operation of the cells at higher temperatures. The apparatus also provides means for equilibration of vanadium or tantalum wire samples in sodium at the higher temperatures. The equilibrated wire samples will be analyzed for oxygen by an internal-friction technique.

Fig. I.C.1. Schematic Drawing of Apparatus for Studies of the Effect of a Dissolved Getter on Oxygen in Sodium

The present experiments are being conducted at 350°C. The cells have been in operation for about five weeks, and their responses have been reproducible for various oxygen concentrations in sodium. The cells are being calibrated against the concentrations of oxygen in sodium. The oxygen concentrations are determined by analysis of the residues from vacuum distillation of sodium samples taken by dip sampling. A plot of the logarithm of the oxygen concentration versus the cell emf is shown in Fig. I.C.2 for the two cells.

The data in Fig. I.C.2 for cell No. 288 compare well with the theoretical relation between emf and oxygen concentration:

$$E = 1.213 - 0.062 \log C,$$

where E is the cell emf in volts and C is the oxygen concentration in ppm by weight. The data for cell No. 287 fall below the theoretical values, but the slope of the line for this cell is near the theoretical slope.

Fig. I.C.2

Oxygen Concentration
Sodium vs Cell Emf

Oxygen is removed from the sodium by uranium gettering. Oxygen additions are made in the form of a 5 v/o O_2 -Ar gas mixture or as Na_2O_2 . Calcium additions will be made as high-purity metallic calcium supplied by Nelco Metals. The experimental studies will cover oxygen concentrations of 2-30 ppm by weight and calcium concentrations of 0-200 ppm by weight in sodium for temperatures between 350 and 700°C.

2. Instrumentation and Control

a. FFTF Instrumentation

(i) In-Core Flowmeter (T. P. Mulcahey)

(a) Tests of Model Probe-type Eddy-Current Flow-sensors

Last Reported: ANL-7581, pp. 31-33 (June 1969).

Five eddy-current (EC) probes have been designed, built, and partly tested. Numbers 2 and 3, which have Inconel coil forms, were made for the droptests in sodium. Number 4 is like No. 2, but was modified for tests in the small sodium loop. Number 5, which has a ceramic coil form, was made for tests in the CAMEL Loop. All probe coils were made to fit in the oscillating test rig (see Progress Report for April-May 1969, ANL-7577, pp. 47-50) for initial tests.

The droptests of EC probe No. 2 in sodium were completed. The maximum probe velocity attained during the test was 10 ft/sec at 1000°F, with the last 9 in. at nearly constant velocity.

The block diagram in Fig. I.C.3 shows the instrumentation used for the droptests. The magnetic pickup generates the velocity information; the scope trigger switch is located near the top of the drop mechanism. When the probe support is released for a drop and the probe moves downward $\sim 1/8$ in. the trigger switch is actuated and initiates a single horizontal sweep of the scope. The EC probe generates the flow signal, which increases in amplitude with probe velocity. The balance control is used to balance out any zero-flow signal due to inherent unbalance of the EC probe. The tunable filter was found to be unnecessary. Another oscilloscope was used to monitor the EC probe excitation current. Four channels of an eight-channel FM tape recorder were used to record the excitation current, flow signal, velocity signal, and 60-cps time base. The tape can be played back into a multichannel strip chart recorder at 0.01 of the recording speed, thus spreading the data over a much greater distance and enabling accurate velocity measurement.

During the test it was observed in the oscillograph traces that, at 800°F and up, some noise occurred at the beginning and end of the drop. The results of a droptest run with no primary drive current showed no measurable pickup due to motion of the probe. It was surmised and later verified that the 150-200 droptests that had been run had loosened the coils and the turns were shorting intermittently. One possible cause of the problem was that, during fabrication, a 0.004-in.-thick high-temperature plastic material was used as insulation between the coil form and the inside diameter and both sides of each coil; then the dry wound coil spaces were filled with a ceramic cement that was expected to cure at less than 1000°F, but 1500°F was needed. It is believed that this caused the high-temperature plastic to vaporize and contribute to the loosening of the coils.

The parameters varied during the droptests include excitation frequency, excitation current, and the temperature of the test system. The results include the determination of the optimum excitation frequency for the probe tested for each test temperature from 470 to 1000°F. An interesting observation from this determination is that if one makes the frequency in Hertz numerically equal to the temperature in degrees F, the flow sensitivity is nearly the same from 470 to 600°F (3.7 mV/ft/sec) and from 800 to 1000°F (2 mV/ft/sec). However, there is a large unexplained gap between 600 and 800°F. Unfortunately, this discrepancy was not observed during the course of tests, partially due to the nature of the data acquisition and to the lack of time.

EC probe No. 3 was tested in the dry oscillating rig. It had considerably more signal distortion and approximately four times the sensitivity of probe No. 2. The sensitivity increase was expected because probe No. 3 had approximately four times as many secondary turns as probe No. 2.

Fig. I.C.3. Instrumentation for Droptests in Sodium of EC Probe No. 2

EC probe No. 4 was tested in a small sodium loop that has a vertical test section of 2-in. Schedule-40 Type 304 stainless steel pipe, 38 in. long, whose top is flanged to accept a probe. The loop had an electromagnetic (EM) flowmeter with a calculated calibration of $0.49 \pm 10\%$ mV/gpm, and was limited to 350°F and 65 gpm. This probe was tested up to 40 gpm before the signal became extremely erratic; after the system was cycled several times up to 60 gpm, most of the noise disappeared. The noise could be due to bubbles or impurities in the sodium; tapping and bumping the probe and test section did not create any noise. The temperature of the sodium was held to approximately 300°F. The optimum frequency of the drive current was determined to be 475-500 Hz.

To show very short-term stability, the EC flowmeter output was compared to the loop EM flowmeter output by starting at zero flow, then holding for a minute or so at each flow step. An upper limit of 65 gpm was used because this is near the limit of the pump. Then the flow was reduced to zero to show the zero-flow reproducibility over a short interval of time. A repeat test was run up to 60 gpm and back to zero for further proof of reproducibility. Both the EC and EM flowmeters exhibited the same flow-signal sensitivity (4 mV/ft/sec). The average peak-to-peak noise appears to be approximately 3-4% of the signal.

Further tests were run with the drive current doubled. The results showed that the EC flowmeter flow-signal sensitivity also doubled. The signal-to-noise ratio remained the same.

During these tests in the small sodium loop EC-flowmeter signals were recorded with and without using a tunable filter. The results showed a definite advantage to use of the filter; without a filter there was a dc offset that is difficult to compensate for.

Balance-stability versus temperature tests were performed with probes Nos. 4 and 5 in a free-air furnace from 100 to 1000°F. In each test the probe signal was balanced out at 100°F. Tests with probe No. 4 showed a sharp peak at 675°F. Tests with probe No. 5 showed a greater initial unbalance and poorer balance stability in the whole range of temperatures than those for probe No. 4. Probe No. 5 also exhibited a sharp peak, but at 510°F instead of 675°F. These sharp peaks might be due to a transition point in one or more of the local materials.

The CAMEL Loop is being checked out with an EC probe of the No. 5 design installed. The loop test section in which the probe is placed is 4-in. Schedule-10 Type 304 stainless steel pipe, 48 in. long. The probe is located on the axis such that the coil is 38 in. back from the entrance end. The front of the probe is supported by a 3-vane structure. Figure I.C.4 shows the method of mounting the probe in the test section.

Coil leads to be 24 in. long from coil form

Fig. I.C.4. Method of Mounting Probe-type EC Flowsensor No. 5 in CAMEL Loop Test Section

The sodium flowrates available range up to 270 gpm; with some loop modifications, flowrates might reach 350-400 gpm. Installation of a 3.8-in.-ID test section is planned; this modification will give a 30% higher flow velocity. The loop has been operated up to 600°F; it is believed that the loop eventually can reach 1200°F.

During loop check-out, limited flowtests with respect to temperature and velocity were performed. The results of measuring probe output versus excitation frequency at fixed velocity and three temperatures indicates a broad frequency response. These tests will aid in determining an optimum frequency for a set of conditions. Other results of probe output versus flow velocity at a fixed frequency and three temperatures indicate that the linearity is good for a given temperature.

The attainment of stability appears to be the greatest problem. Because material effects are believed to be the predominant stability variable, they are to be studied in more detail. It appears that metallic coil forms might produce the best probe stability.

(ii) Gas Disengagement for Failed-Fuel Monitoring
(E. S. Sowa)

(a) Tests of Gas Disengagement

Last Reported: ANL-7595, pp. 33-34 (July 1969).

Tests were performed in the Failed-fuel Detection Loop (FFDL) in the slow-flow injection series at a sodium temperature of 500°F (compared to 1000°F for preceding experiments). Injections were made when sodium flowrates were 7, 5, and 3 ft/sec. The results reflected the effect of increased viscosity, surface tension, and density of the sodium at the lower temperature. For example, at 500°F and 5 ft/sec, all the released activity was carried to the surge tank; at 1000°F and 5 ft/sec, recovery was ~36%. At 3 ft/sec, some activity carried over to the surge tank at 500°F, but none appeared at this velocity for the 1000°F test.

(b) Bubble-size Experiment

Not previously reported.

Photographs taken of bubbles flowing in water in horizontal lines showed the effect of the $\rho V^2/2$ force. At a velocity of 0.5 ft/sec, the bubbles were relatively large, although they traveled freely along with the flow stream. At 2.0 ft/sec, the bubbles were considerably smaller because of the imposed hydrodynamic impact.

In lines tilted downward at 45°, photographs show that bubbles are carried downward with some resistance at 1 and 2 ft/sec, but two-phase separation occurred at 0.5 ft/sec.

b. EBR-II In-core Instrument Test Facility (E. Hutter)

(i) Preliminary Study of Various Schemes (O. S. Seim, T. Sullivan, J. Pardini, and R. H. Olp)

Last Reported: ANL-7595, pp. 34-37 (July 1969).

(a) Thermocouple Bending and Flexure Tests. When the facility is installed in EBR-II, the thermocouples and the thermocouple leads will extend 34 ft below the operating floor level into the center of the reactor core. Inadequate overhead space above the small rotating plug will preclude a straight withdrawal of the thermocouples from the in-core thimble-assembly guide tube when removing the thermocouples for periodic recalibration and reinsertion into the core for continued testing. The lack of adequate overhead space has led to the investigation of a reel type of storage and handling device, which would loop the thermocouple leads into a reasonably small-diameter coil as the leads are withdrawn from the thimble. The storage reel also could be used to transport the thermocouples to the calibrating station. Since a storage reel will impose flexing and bending stresses on the thermocouple leads, tests are being conducted to determine the optimum diameters of the reel and the thermocouple leads.

Thermocouple-vendor literature indicate that an acceptable bending radius is approximately 500 times the OD of the thermocouple sheath. This would equate to a 10-ft-dia coil bend for a typical 1/8-in.-OD Type 304 stainless steel-sheathed thermocouple with mineral insulation.

Experimental wrapping of a thermocouple of this type on a 4-ft-dia storage reel indicates that the 1/8-in.-OD lead assumes a 10-ft-dia permanent set when removed from the reel. Electrical checks were made at the beginning, during, and at the completion of these bending tests to establish the resistance between the insulation and the outer sheath, and the loop continuity and resistance of the internal thermocouple wires. The bending tests were conducted at room temperature, with thermocouples heated to 700°F, the average operating temperature of the primary-tank sodium. A series of 10 bending cycles was run for each thermocouple. Each cycle consisted of heating the thermocouple to 700°F in a 34-ft-long furnace, withdrawing and wrapping it on a 4-ft-dia reel, and then unwrapping and reinserting the thermocouple into its guide tube in the furnace.

Since it is expected that each thermocouple tested in the facility will be calibrated no more than 3 times during its lifetime, a

series of 10 bending test cycles was chosen as sufficient for checking the effects of bending on the stainless steel sheath, the mineral insulation, and the integrity of the internal thermocouple wires.

Tests to date have been conducted with 1/8-in.-OD (nominal) and 0.0986-in.-OD thermocouples. The results show no apparent lowering of insulation resistance, no leaks developing in the sheath, and no loss of loop conductivity of the thermocouple wires.

Additional tests are scheduled for various sizes (OD) and material types of thermocouples.

3. Fuel Handling, Vessels and Internals.

a. Core Component Test Loop (CCTL) (R. A. Jaross)

Last Reported: ANL-7595, p. 39 (July 1969).

(i) Loop Modifications to Accommodate Second FFTF Subassembly. Modifications to the CCTL to accommodate the FFTF Mark-II fuel assembly and steps to improve loop reliability are proceeding.

Two of the 12 welds required to install the 2-in. bypass pipe between the overflow surge and the suction of the mechanical pump have been made and radiographed. The radiographs are being evaluated. The fittings, pipe, and flow-control valve are available to complete the pump overflow bypass; although procurement of an acceptable 2-in. flow-control valve was difficult (eight available 2-in. bottom-seal valves were radiographed to identify one valve that could meet the specifications for Class-2 castings).

Eight of the 12 welds required to install the 4-in. Venturi-type flowtube have been made. Two of these welds have been radiographed and approved; the other six welds are being radiographed. The CCTL plugging loop and sodium sample station have been redesigned, and construction has started.

The gas chromatograph has been calibrated. With a standard-reference gas bottle, peaks of 72 ppm CO₂, 41 ppm CH₄, 80 ppm N₂, 82 ppm O₂, and 7 ppm H₂ have been recorded with reasonable statistical repetition.

Fabrication of components that will be used to modify the test vessel so it can accommodate the FFTF test subassembly is ~25% complete. Of the 27 original piping welds that were exposed during the non-destructive visual examination of all CCTL drain valves, 18 have been

radiographed again; all 18 welds meet original CCTL fabrication specifications. After all the valve welds have been radiographed, devices to detect sodium leakage will be installed on five drain valves. The devices consist of a ceramic-loaded nichrome wire wrapped in series around each valve weld, the vertical length of the valve body, and the bonnet.

Metallurgical tests, measurements, and evaluation of loop materials to determine the condition of the CCTL loop to operate for subsequent testing have been completed. An evaluation report is being prepared.

D. Systems and Plant Development

1. Plant and Design

a. Contract Management, Technical Review, and Evaluation (L. W. Fromm and K. A. Hub)

Last Reported: ANL-7595, p. 40 (July 1969).

(i) Evaluation of 1000-MWe Follow-on Study Task Reports.

The Task-II, -III, and -IV reports of Babcock & Wilcox were given patent clearance and are in the process of publication.

The evaluation of the Westinghouse Task-I report was completed and is being reviewed by the evaluations personnel.

The Task-II, -III, and -IV reports of all contractors are being evaluated. Approximately 15% of the final evaluation report has been drafted.

E. EBR-II--Research and Development

1. Instrumented Subassemblies (E. Hutter and A. Smaardyk)

a. Preheating of Instrumented Subassembly (C. Divona)

Not previously reported.

Tests have indicated that when an instrumented-subassembly capsule is heated in such a manner that the sodium bond melts from the bottom upward, a temporary displacement of the element tube occurs (see Progress Report for April-May 1969, ANL-7577, pp. 82-83). To avoid this situation, plans have been made to preheat the instrumented subassembly in a special furnace and insert it into the primary tank while the bond sodium is molten.

The furnace for preheating the instrumented subassembly has been fabricated and tested with an instrumented subassembly containing 17 dummy capsules and 2 sodium-bonded capsules fabricated to the exact specification of the prototypal capsules. One bonded capsule was located at the center of the bundle and another at a corner position (see Fig. I.E.1). Both capsules contained thermocouples at the top and bottom of the bond length.

Tests indicated that the bond of both capsules melted from the top to the bottom. After 3 hr in the furnace, the difference in bond temperatures at the top and the bottom of both the center and the outside capsules was 113°F (see Fig. I.E.1).

The subassembly was then removed from the furnace and allowed to cool at room temperature (approximately 75°F). The first solidification of bond occurred 36 min after removal from the furnace.

2. Experimental Irradiation and Testing (R. Neidner)

a. Experimental Irradiations

Last Reported: ANL-7595, pp. 45-47 (July 1969).

Table I.E.1 shows the status of the experimental subassemblies in EBR-II on August 15.

The following five experimental subassemblies were removed from the grid after Run 36:

Fig. I.E.1. Sodium-bond Temperatures of Instrumented Subassembly during Preheating and Cooling

TABLE I.E.1. Status of EBR-II Experimental Irradiations as of August 15, 1969.

Subassembly No. and (Position)	Date Charged	Capsule Content and (Number of Capsules)	Experi- menter	Accumulated Exposure (MWd)	Estimated Goal Exposure (MWd)	Burnup ^a
XG04 (7B1)	7/16/65	UO ₂ -20 wt % PuO ₂ (2) Stainless Dummies (17)	GE	24,845	45,000	6.2
XO12 (4B2)	8/10/66	UO ₂ -20 wt % PuO ₂ (19)	NUMEC	17,615	21,400	10.1
XO20 (6B5)	1/13/67	UO ₂ -PuO ₂ (9) UC-20 wt % PuC (3) Structural (4) Structural (2) Graphite (1)	GE UNC PNL ANL PNL	14,808	13,000 ^b	6.0 6.6 4.1 4.1 4.1
XO21B (2D1)	2/23/69	Structural (6) Structural (1)	PNL PNL	14,209 5,245	23,200 9,000	2.2 + 4.0 ^c = 6.2 2.2
XO27 (4B3)	11/21/67	UO ₂ -25 wt % PuO ₂ (18) Structural (1)	GE PNL	12,131	16,000	6.8 5.2
XO32 (6E5)	11/22/67	UO ₂ -25 wt % PuO ₂ (19)	PNL	12,434	14,300	5.2
XO33 (5E2)	12/22/67	UC-20 wt % PuC (19)	UNC	11,278	12,200	5.5
XO35 (7B3)	4/13/68	Structural (7)	ORNL	11,243	44,800	2.8
XO36 (7E1)	7/25/68	UO ₂ -25 wt % PuO ₂ (19)	GE	9,529	33,300	2.5
XO38 (7C5)	5/7/68	Structural (7)	INC	10,735	17,700	2.4
XO41 (7A3)	7/24/68	Structural (7)	PNL	9,195	16,700	2.0
XO42A (7D5)	4/2/69	Ta (1) Ta (2) B ₄ C (2) B ₄ C (2)	PNL PNL PNL PNL	9,008 4,645 9,008 4,645	27,800 23,500 27,800 23,500	1.0 + 1.0 ^c = 2.0 1.0 1.0 + 1.0 ^c = 2.0 1.0
XO43 (4D2)	2/20/69	UO ₂ -25 wt % PuO ₂ (37)	GE	5,245	6,100	2.9
XO44 (7A1)	9/28/69	Oxide Insulator (1) Stainless Dummies (6)	LASL	7,870	12,000	1.4
XO50 (4C2)	2/23/69	UO ₂ -20 wt % PuO ₂ (4) UO ₂ -28 wt % PuO ₂ (4) UO ₂ -20 wt % PuO ₂ (5) UC-18 (2) Structural (4)	GE GE ORNL W GE	5,245	7,500	2.97 + 7.7 ^c = 10.6 2.8 2.9 2.9 1.7 + 5.3 ^c = 7.0
XO51 (3A2)	12/16/68	UO ₂ -25 wt % PuO ₂ (37)	PNL	5,790	16,400	1.2
XO54 (4E1)	3/31/69	UO ₂ -25 wt % PuO ₂ (37)	PNL	4,645	10,000	2.5
XO55 (6A4)	2/23/69	UC-15 wt % PuC (19)	UNC	5,245	20,000	1.7
XO56 (5C2)	4/2/69	UO ₂ -25 wt % PuO ₂ (37)	GE	4,645	10,600	2.3
XO57 (2B1)	2/23/69	Structural (7)	PNL	5,245	15,000	2.2
XO58 (6F1)	4/24/69	UO ₂ -25 wt % PuO ₂ (37)	GE	4,069	16,000	1.5
XO59 (4A1)	4/23/69	UO ₂ -25 wt % PuO ₂ (37)	PNL	4,069	17,500	1.4
XO60 (7C3)	4/3/69	Structural (7)	INC	4,645	5,400	1.0
XO61 (7A5)	4/23/69	Structural (7)	INC	4,069	18,000	0.8
XO62 (6F3)	5/23/69	UO ₂ -25 wt % PuO ₂ (37)	GE	2,937	13,400	1.3
XO63 (7F5)	6/28/69	Magnetic Materials (7)	ANL	1,735	5,400	0.3
XO64 (4F2)	5/28/69	UO ₂ -25 wt % PuO ₂ (19)	GE	3,937	10,700	2.2

^aApproximate accumulated center burnup on peak rod (fuels, at. %; nonfuels, nvt x 10⁻²²).^bSpecial extension of XO20 through Run 37 while XO19 is under examination.^cPrevious exposure from another subassembly.

Subassembly No.	Position	Content of Capsules or Elements	Number of Capsules or Elements	Experimenter	Burnup*
XG03	7D1	UO ₂ -20 wt % PuO ₂	2	ANL	5.4
		Stainless Dummies	17		
XO19	6D2	UO ₂ -20 wt % PuO ₂	7	GE	5.1
		UC-20 wt % PuC	3	UNC	5.5
		Structural	8	PNL	3.8
		Graphite	1	PNL	3.8
XO34**	2F1	Structural	7	ORNL	5.2
XO65**	7E5	Pressurized Tubes (creep test)	23	ANL-EBR-II	0.2
XO67	4A3	Weldments	4	PNL	0.9
		Structural	1	GE-NSP	0.9
		Structural	1	ORNL	0.9
		Oxide Insulator	1	ORNL	0.9

b. Nondestructive Testing Materials

Not previously reported.

(i) Pulsed Electromagnetic Test Equipment for Inspection of Capsules and Components (C. J. Renken)

New transducers have been constructed for the pulsed electromagnetic tubing-inspection equipment recently received by EBR-II. Operation of these transducers, which are designed to measure wall thickness, has been checked out with the EBR-II inspection equipment. Wall-thickness measurements to less than 0.005 mm appear to be practical in tubing with a 0.5-mm or thinner wall.

Test equipment capable of testing sodium bonds in irradiation capsules while the sodium is molten is being fabricated. Similar equipment already is in use in the Fuel Cycle Facility and at Illinois. The equipment can detect bond defects in the fuel element independently of any bond defects in the capsule sodium. The equipment is about 50% complete.

c. Safety Review of Experiments (F. D. McGinnis)

Last Reported: ANL-7595, pp. 47-49 (July 1969).

To determine the orifice size for a controlled-flow, half-worth driver subassembly, flowtests were made with a prototypal driver subassembly having the model-STB axial blanket. An orifice size of 0.980 in. has been specified to provide two-thirds of the flowrate in a standard driver subassembly in Rows 1 and 2.

*Approximate accumulated center burnup on peak rod (fuels, at. %; nonfuels, nvt x 10⁻²²).

**Requested for reconstitution.

3. Materials-Coolant Compatibility (D. W. Cissel)

a. Evaluation and Surveillance of EBR-II Materials (W. E. Ruther and S. Greenberg)

Last Reported: ANL-7595, p. 50 (July 1969).

(i) Corrosion of Irradiated Nickel. The corrosion weight losses of unclad nickel rings from the first of two irradiated subassemblies containing such specimens have been measured (see Table I.E.2) and evaluated. The results are considerably more favorable toward the use of unclad nickel than had been anticipated from available solubility data. If a linear extrapolation of the data is made, a weight loss of about 1/2 g per subassembly per year is anticipated. This loss should be acceptable. A linear extrapolation of the maximum dissolution rate measured gives 0.02 mil/yr.

TABLE I.E.2. Weight Losses of Nickel Rings^a Exposed for 2910 MWd in Position 7F5

Ring ^b	Weight Loss (mg/cm ²)	Ring ^b	Weight Loss (mg/cm ²)	Ring ^b	Weight Loss (mg/cm ²)
1	0.061	11	-	21	0.028
2	0.065	12	0.027	22 ^c	0.053
3	0.049	13	0.050	23	0.035
4	0.062	14	-	24	0.067
5 ^c	0.019	15	-	25	0.011
6	0.044	16 ^c	0.024	26	0.041
7	0.044	17	0.030	27	0.026
8	0.059	18	0.014	28 ^c	0.020
9	0.051	19	0.026	29	0.021
10 ^c	0.007	20	0.036	30	Scratches precluded meaningful measurement

^aRings were of 2.16-in. OD and 2 in. long; a total area of 88 cm² had been exposed to sodium flowing at 1.2 gpm.

^bRing No. 1 is the top ring, No. 30 the bottom.

^cRing was chromium-plated.

The second of the two subassemblies containing unclad nickel specimens will be removed from EBR-II in March 1970 after a total exposure of a year.

(ii) Examination of Control Rod 6. The parts of control-rod assembly 6 that had been exposed to primary EBR-II sodium have been examined metallurgically. Special attention was paid to possible decarburization of the parts. No evidence of extensive decarburization was found, although a zone approximately 0.001 in. thick on an unplated portion of a Type 420 stainless steel jaw gripper appeared to have a reduced carbon content. The Rex AA tool steel pin appeared to be unaffected by the sodium exposure.

b. Effect of Interstitial Elements in EBR-II Sodium

Last Reported: ANL-7595, p. 50 (July 1969).

A second set of refractory metal wires is being exposed to EBR-II coolant during reactor run 38. Included in this experiment are wires of niobium, vanadium, V-10 wt % Cr, and V-20 wt % Cr.

c. LMFBR Materials Evaluation (W. E. Ruther)

Not previously reported.

A high-temperature material-testing subassembly is being designed for Row 7 of EBR-II. A portion of the sodium flow through the subassembly will be heated to temperatures above 1200°F by passing the sodium through a thermally insulated gamma-heat susceptor. This high-temperature sodium will flow over the test specimens. Mechanical design has been completed; heat generation and transfer are being calculated to determine the required sodium flow.

4. Systems Engineering (B. C. Cerutti)

a. Surveillance, Evaluation, and Studies of Systems

Last Reported: ANL-7595, pp. 51-52 (July 1969).

(i) Rotating Plugs (L. P. Cooper)

The fast and slow rotating speeds of the large and small rotating plugs of the reactor were determined by test. The fast speeds are 87 and 53 in./min, respectively, for the large and small plugs; the slow speeds are 24 and 20 in./min, respectively. (The speeds given are those at the OD of the blades.)

The freeze seals of the large and small plugs were inspected. The depth of the alloy in the large-plug seal trough was 7 in.; that in the small-plug seal trough was $8\frac{3}{4}$ in. A small amount of very

fine and powdery dross was in each trough. Cleaning was not required. Sixty-five round-trip transfers have been made since the troughs were last cleaned. It is estimated that 100 more round-trip transfers can be made before cleaning becomes necessary.

5. Reactor Analysis, Testing and Methods Development (R. R. Smith)

Last Reported: ANL-7595, pp. 54-63 (July 1969).

a. Cladding Temperature during a Gas Release from an Oxide Fuel Element (J. F. Koenig)

To determine the probability of cladding failure being propagated from one fuel element to an adjacent element, the temperature distribution was determined for a hypothetical fuel element whose cladding was insulated during a release of the gaseous fission products.

A fuel element was assumed to have ruptured and its fission-gas inventory released to the coolant channel. A worst-case heat-transfer condition was assumed in the channel where the gas insulated a portion of the circumferential surface of the element. The heat transfer through the insulated arc was assumed to be essentially zero, thereby requiring the heat to be conducted circumferentially in the fuel and cladding for the portion under the gas blanket. For a relatively fast gas release, two-phase flow would probably not be established, and the surface could be insulated by a gas bubble. For a slower release, the gas would probably mix with the coolant, and some heat transfer from the cladding surface to the two-phase mixture would occur.

Computations were based on a fuel element having a wall thickness of 0.015 in. and an outside diameter of 0.290 in. Fuel consisted of 80% UO_2 -20% PuO_2 pellets. The element was assumed to operate at a heat rating of 16 kW/ft, and to be cooled by sodium at a temperature of 850°F and flowing at 12 ft/sec. These parameters represent average conditions for a mixed-oxide fuel element at the centerline of the EBR-II core.

The fuel was assumed to have expanded and to be in contact with the cladding, and the fuel-to-cladding conductance was set at 1500 Btu/hr-ft²-°F. The fuel was assumed to be composed of a central void, a high-density columnar-grain region, a lower-density equiaxed region, and an outer region of the oxide at its original density. Calculations were made both for 92 and 82% theoretical density to cover the variations in the densities of the mixed-oxide experiments.

The temperature distribution and grain radii in a normal fuel pin are given in Table I.E.3.

TABLE I.E.3. Calculated Temperatures and Grain Radii of
Oxide Fuel Element Operating at 16 kW/ft

Fuel density, % of theoretical	92	82
Maximum fuel temperature, °F	4580	4360
Fuel-surface temperature, °F	1530	1530
Void radius, in.	0.022	0.039
Columnar-grain radius, in.	0.066	0.071
Equiaxed-grain radius, in.	0.092	0.097
Original-density radius, in.	0.125	0.125

Steady-state two-dimensional temperature distributions were obtained from the THTB program for different arcs of blanketing of the cladding surface. After a 100° arc of the surface of the fuel element had been covered, the maximum cladding temperature was 2650°F for the element containing 82%-theoretical-density fuel and 2600°F for the element containing 92%-theoretical-density fuel. Because the melting temperature of Type 304 stainless steel is 2550-2650°F, the cladding of the fuel element would melt. Fuel-element failure may occur at a smaller arc of gas coverage, however, because of the low tensile strength of the cladding at the elevated temperatures.

The time required to heat the cladding to its melting temperature was calculated by using the TOODEE program. The results of this calculation are shown in Fig. I.E.2. The cladding temperature rises to 2000°F in less than 2 sec and to its equilibrium value in less than 20 sec. Since sustained gas release from a high-burnup fuel element could continue for 20 sec, it is concluded that failure mechanisms based on gas release must be treated with concern, particularly if the gas bubble covers a 100° arc of the surface of the fuel element and if the surface is insulated by the bubble.

Fig. I.E.2. Maximum Cladding Temperatures during Gas Release
from an Oxide Fuel Element (from TOODEE Program)

b. Rod-drop Studies (I. A. Engen)

To study the possibility of changes in reactivity feedback during typical operating cycles, rod-drop experiments were conducted at the beginning and end of Runs 35 and 36. In all cases the measurements involved the modified drop-rod previously described in the Progress Report for June 1969, ANL-7581, pp. 36-38.

The results of rod-calibration tests made at 500 kW are summarized in the following table:

<u>Time When Tests Were Made</u>	<u>Rod Worth (\$)</u>
Beginning of Run 35	0.02003
End of Run 35	0.01978
Beginning of Run 36	0.02206
End of Run 36	0.02208

Although an apparent real change in rod worth between the beginnings (and ends) of Runs 35 and 36 is evident, the calibration data shown indicate that the rod worth does not change significantly during a given run. The indicated change in rod worth from one run to another probably can be explained in terms of changes in core composition and configuration in the vicinity of the drop rod.

Using the calibrated values for rod worth, the feedback function established from the data taken at the beginning of Run 35 was fitted to a time-dependent feedback model in a manner described by Hyndman and Nicholson.* The model, along with values established for time constants and feedback amplitudes, is given in Fig. I.E.3. In the model described, the following convention has been used: a positive sign is used for a negative feedback; a negative sign indicates positive feedback.

With the use of the model described in Fig. I.E.3 (with the identical values for time constants and feedback amplitudes), the calibrated worths of the drop rod, and the measured shape of the power trace, the feedback functions for all other rod-drop tests at 50 MWt were predicted. The results of these attempts are summarized in Figs. I.E.4 through I.E.6.

Inspection shows that the predicted feedback for the beginning of Run 36 agrees with experimentally measured values. For the ends of Runs 35 and 36, however, a consistent discrepancy is indicated, the sense of the discrepancy being such that the predicted feedback is higher than

*Hyndman, R. W., and Nicholson, R. B., The EBR-II Feedback Function, ANL-7476 (July 1968).

Fig. I.E.3. Fit of Rod-drop Reactivity Data (from beginning of EBR-II Run 35) to Hyndman-Nicholson Feedback Model

Fig. I.E.4. Fit of Rod-drop Reactivity Data (from end of EBR-II Run 35) to Hyndman-Nicholson Feedback Model

Fig. I.E.5. Fit of Rod-drop Reactivity Data (from beginning of EBR-II Run 36) to Hyndman-Nicholson Feedback Model

Fig. I.E.6. Fit of Rod-drop Reactivity Data (from end of EBR-II Run 36) to Hyndman-Nicholson Feedback Model

that measured experimentally. Whether the indicated discrepancy is real or the result of uncertainties in the values used for the worth of the drop rod is unclear. It is conceivable, however, that the discrepancy is real and may be the result of physical changes in the fuel during a given run.

Rod-drop studies at the beginning of Run 37 have been conducted. The results of these studies will be compared with those established at the end of Run 37.

c. Dynamic Simulation of EBR-II Rod-drop Data (A. V. Campise)

A kinetics study has been initiated to analyze the EBR-II rod-drop experimental data by the use of the AIROS dynamic-simulation program. This program is based on space-independent kinetics, and is capable of describing the radial and axial heat transfer in a multifuel-channel model. In addition, it allows for temperature-induced reactivity feedbacks to be automatically computed and inserted in the closed-loop dynamic-feedback model.

The model chosen to analyze the EBR-II rod-drop experiments basically represents the material composition of the EBR-II reactor as driver fuel, blanket metal, and sodium coolant. The overall temperature coefficients for the core and blanket were obtained from ANL-7513,* which reports the results of using the latest nuclear models and group cross sections to compute the fuel and coolant coefficients based on axial fuel expansion and on changes in sodium density affecting the neutron leakage from the reactor core. The model represents each driver-fuel row of the reactor in terms of the average driver-fuel element in that row. The overall temperature-induced reactivity coefficients are distributed over each row according to normalized statistical weighting functions obtained from early ZPR-3 mockup experiments that simulated EBR-II with sodium included. The thermal conductivity and heat capacity as functions of temperature were obtained from ANL-6116** and ANL-6702.† Thermophysical properties of sodium were those of Golden and Tokar.†† The densities of the various materials also were included as input data. Therefore, the basic input to this model is a detailed representation of the average fuel element in each row of the core and inner blanket along with the temperature-induced reactivity feedback from each row in the core and inner blanket. The basic input data consist of:

* Reactor Development Program Progress Report for October 1968, ANL-7513, p. 46.

** Zegler, S. T., and Nevitt, M. V., Structure and Properties of Uranium-Fissium Alloys, ANL-6116 (July 1961).

† Savage, H., and Seibel, R., Heat Capacity Studies of Uranium-Fissium Alloys, ANL-6702 (Sept 1963).

†† Golden, G. H., and Tokar, J. V., Thermophysical Properties of Sodium, ANL-7323 (Aug 1967).

1. dimensions of the fuel pin, bond, cladding, and sodium-coolant annulus;
2. density, thermal conductivity, and heat capacity of the fuel, cladding, sodium bond, and coolant as functions of temperature;
3. the computed temperature coefficients due to axial expansion of driver fuel and to changes in sodium density in the reactor core and blanket;
4. a normalized statistical-weighting function for the distribution of the overall temperature coefficients due to fuel and coolant (obtained from the ZPR-3 critical experiments simulating EBR-II containing sodium); this weighting function can be improved with additional ZPR-3 criticals for the present core loadings;
5. the computed power and flow conditions for each row of the reactor and blanket;
6. delayed-neutron data yielding excellent agreement with basic reactor-kinetics studies of EBR-II;
7. computed prompt-neutron lifetime for the EBR-II reactor;
8. the measured worth of the stainless steel rod and the time duration for insertion in a given rod-drop experiment.

Preliminary results from use of this dynamic model for Run 33A under conditions of 50 MWt with 100% coolant flow and of 27.5% MWt with 100% coolant flow are depicted in Figs. I.E.7 and I.E.8, respectively. Since the dynamic model used is a multiparameter model incorporating existing knowledge of the EBR-II reactor, the excellent agreement is not fortuitous, but indicative of the dynamic properties of the EBR-II core. The agreement is well within the uncertainties of the measurements.

In the case of 50 MWt with 100% coolant flow, the AIROS dynamic-simulation program was used to compute more than 40 sec of experimental data after the rod drop, until a very long reactor period was achieved. In this way it was possible to compare the computed quasi-steady-state power coefficient with that obtained from static measurements of the power-reactivity decrement (PRD). The computed power coefficient was ~ 1.5 lh/MWt as compared with a measured coefficient of 1.6 lh/MWt. This result implies that between the accumulation of 40-sec rod-drop data and the 1/2- to 1-hr equilibrium condition used in obtaining the PRD data, additional negative reactivity is introduced into the reactor. Experimental programs are now being devised to permit better identification of the probable areas in the reactor vessel and blanket associated with this additional negative feedback.

Fig. I.E.7. AIROS Simulation of EBR-II Rod-drop Experiment for EBR-II Run 33A
(50 MWt; 100% coolant flow; worth of drop rod, $\$0.053 \pm 0.0025$)

Fig. I.E.8. AIROS Simulation of EBR-II Rod-drop Experiment for EBR-II Run 33A
(27.5 MWt; 100% coolant flow; worth of drop rod, $\$0.053 \pm 0.0025$)

In the case of 27.5 MWt with 100% coolant flow, a similar comparison with PRD data was made. The computed quasi-steady-state power coefficient was ~ 2.0 lh/MWt as compared with a measured coefficient of ~ 1.7 lh/MWt. The preliminary implications resulting from this comparison are that a positive delayed reactivity insertion follows the 40 sec of rod-drop data and shows up only in the 1/2- to 1-hr equilibrium conditions used in obtaining the PRD data. This implication seems to be in agreement with the results of earlier calculations of fuel-subassembly bowing, which indicated the possibility of inward motion of fuel subassemblies at lower power levels. Additional calculations are planned for the core loadings of Runs 26B and 29A, which included a stainless steel blanket, and Runs 29C, 33A, and 36A, which included a uranium blanket. The calculations will consider various power and flow conditions.

Initial comparisons of data obtained with the new high-speed, low-worth stainless steel drop rod used for the first time in Run 36A (see Fig. I.E.9) showed the same excellent agreement as obtained in Run 33A.

Fig. I.E.9. AIROS Simulation of EBR-II Rod-drop Experiment for EBR-II Run 36A (50 MWt; 100% coolant flow; worth of drop rod, $\$0.020 \pm 0.001$)

d. The Reactivity Effect of Plutonium (E. M. Dean and J. K. Long)

For some time it has been observed that the loss in reactivity with burnup is about 0.15 lh/MWd at the start of a run and that it drops to about 0.12 lh/MWd after about a week of operation, remaining approximately

constant for the balance of the run. It has been reasoned that this change in burnup rate results from generation of plutonium in the core and blanket through the beta decay of ^{239}Np (2.3-day half-life). Neptunium-239, presumably a threshold fissile isotope, has a negligible worth compared with that of ^{239}Pu . During the first few days of a run, no plutonium is generated because the source of parent neptunium has decayed during the intervening shutdown. After a run has been under way for approximately a week, the neptunium component is essentially saturated. Plutonium then is generated in the reactor at a constant rate.

Calculations have verified that the worth of the reactor-formed plutonium is indeed of the right magnitude and time scale to account for the observed changes in burnup rate. Radial reaction rates for capture in ^{238}U and absorption in ^{239}Pu , and the worth in Ih/g of ^{239}Pu , were obtained from a MACH-I calculation. The data obtained were applied to the decay of ^{239}Np to ^{239}Pu with consideration given to the absorption in ^{239}Pu . The results are given in Table I.E.4. The saturation value of the buildup of ^{239}Pu is consistent with the value of 0.03 Ih/MWd inferred from experimental measurements.

TABLE I.E.4. The Effect of Plutonium Buildup in Terms of Reactivity

Time from Start of Run (hr)	Plutonium Buildup Rate (Ih/MWd)	Time from Start of Run (hr)	Plutonium Buildup Rate (Ih/MWd)
0	0	144	0.0299
24	0.0054	168	0.0318
48	0.0135	192	0.0331
72	0.0196	216	0.0341
96	0.0241	240	0.0349
120	0.0275		

e. Coolant-temperature Profile in a Mark-B7 Structural Subassembly (S. M. Masters)

The steady-state heat-transfer code HECTIC was used to establish the coolant-temperature profile in a Mark-B7 structural-irradiation subassembly. As an illustration of typical conditions, computations were carried out for experimental Subassembly XO21 located in grid position 2D1. A sector consisting of one-twelfth of the subassembly cross section and containing five heat-producing surfaces and three coolant channels was used as a computational model. Assumed were symmetry with respect to the remaining 11 sectors, a coolant flow of 12 gpm (427 lb/hr-sector), a power-generation rate of 19.4 kW/subassembly (taken from the experimenter's estimate), a total coolant-flow height of 37.5 in. (13.5 in. in the core and 24 in. in the trilateral blanket structure), and an ambient surrounding temperature of 900°F. Figure I.E.10 shows the

Fig. I.E.10. Profile of Axial Coolant Temperature in Irradiation Subassembly XO21, a Mark-B7 Structural Experiment in EBR-II Grid Position 2D1

results of the computations. The mixed mean outlet temperature as calculated by the code was 851°F.

f. Correction for Rod-bank Expansion (J. K. Long)

The power-reactivity decrement (PRD) as measured includes a component originating from the expansion of the handles of the bank of control rods relative to the core. The effect is expected to be linear with temperature rise of the sodium, but nonlinear with rod position because of the S shape of the curve of rod worth versus position. The first experiments (in Run 26A) devised to verify and to establish

the magnitude of the effect were based on the following approach:

1. A critical position at zero power was found with the controlling rod and with all other rods banked in their normal position, for example, 12 in.
2. A new critical position at zero power was then found with half the banked rods at 10 in. and the other half at 14 in.

Since the effects of rod-handle expansion are negligible at zero power, any difference between these two critical positions originates from the nonlinearity of the rod worth coupled with interaction effects accompanying the rebanking.

If the same two experiments are repeated at a higher power, any additional difference between the critical positions is attributed to the power, operating through the rise in temperature of the sodium to expand the rod handles.

The first experiments have been improved by observing that the S shape of the reactivity-worth curve suggests that there is essentially the same expansion effect for a rod at 14 in. (fully inserted) as for one at 0 in. (fully withdrawn). Thus, the rod-bank comparison can be made between rods at, for example, 10 in. (maximum slope) and a combination of rods at 0 and 14 in. (minimum slope). This approach yields a larger difference in rod-bank effect than the earlier methods indicated and essentially doubles the reliability of the results. The improved experiments can be performed only if there is sufficient excess reactivity available to make the reactor critical with one or more rods fully withdrawn.

A series of the improved experiments was performed in Run 35. The precision of the new method seemed sufficient to justify doing a series of rod-bank-comparison experiments under various conditions of power and flow in an effort to ascertain if the expansion correction was proportional to the temperature rise of the sodium, as had always been assumed. Experiments also were performed both at the beginning and at the end of the run to investigate the effect, if any, of burnup on the expansion correction.

The results of the improved experiments are given in Table I.E.5. The experimental values in the next to the last column are roughly proportional to the temperature rise of the sodium except for the 40-MWt point, which is presumed to be in error. Calculated values in the last column were obtained by the methods outlines in "EBR-II Run 25 and 26A Interim Report."

TABLE I.E.5. Comparison of Experimental and Calculated Reactivity Corrections for Expansion of the Control-rod Handles

	Rod-bank Positions Compared (in.)	Power (MWt)	Flow Fraction	ΔT of Sodium (°F)	Reactivity Difference due to Rod-handle Expansion (1h)	
					Experimental	Calculated
Beginning of Run 35	11 to 14 & 0	20	1	59	8.9	4.8
	11 to 14 & 0	40	1	117	-1.8 ^a	9.4
	11 to 14 & 0	50	1	146	14.2	11.5
	11.5 to 14 & 0	27	1	79	9.2	5.6
	11.5 to 14 & 0	27	0.9	88	9.2	6.3
	11.5 to 14 & 0	27	0.75	106	11.1	7.7
	11.5 to 14 & 0	27	0.54	146	14.7	11.1
End of Run 35 (1080 MWd)	12.5 to 14 & 0	27	1	79	2.8	3.5
	12.5 to 14 & 0	27	0.54	147	6.5	8.5
	12.5 to 14 & 0	50	1	146	6.1	7.8

^aBelieved to be in error.

g. Post-incident Recall System (J. R. Karvinen and R. A. Call)

Four channels of the post-incident recall system (PIRS) are now operational. However, the results of preliminary attempts to connect sensors into the system have indicated that noise bursts (intrinsically associated with the recorder) compromise the quality of the information. In addition, while connecting a subassembly thermocouple and a period channel to the system, 60-Hz noise from the sensor leads prevented satisfactory operation. Further development work is awaiting the delivery of components from the vendor.

h. Transient Response of Safety System (J. R. Karvinen and R. A. Call)

The equipment to provide transient-response data for the EBR-II safety system has been fabricated, and preliminary testing is

under way. The testing of the equipment on the reactor system as well as the testing of the 15 cables of shielded twisted pairs is scheduled for the end of Run 37.

i. Effects of Resonance Scattering on Spatial Energy Variations of Flux in EBR-II-type Systems with a Central Nickel-rich or Iron-rich Subassembly (D. Meneghetti and K. E. Phillips)

Calculations have been made for a core with a radius of 29.0 cm and with the approximate composition of EBR-II, radially surrounded by a 30.0-cm-thick depleted-uranium blanket. In the center was either a nickel-rich or an iron-rich region with a radius of 3.35 cm. For the iron region, the approximate atomic densities in units of 10^{24} at./cm³ were: sodium, 0.003; stainless steel, 0.074. For the nickel-rich region, the approximate atomic densities were sodium, 0.0016; nickel, 0.085.

The spectra were obtained by using 371 equal-lethargy energy groups from 2.1 keV to 1.35 MeV by use of the composite of the Elmoe code and the Argonne discrete SN transport code.* The S_2 analysis, based on cylindrical geometry, was an inhomogeneous calculation using the transport approximation.

A coarse-group calculation was made to obtain a spatially distributed fission-source shape. An approximate correction for axial-leakage effects was made by using fine-energy leakage absorptions. A total of 86 mesh intervals were used, with a greater mesh density near interfaces.

The spectra at various spatial positions are shown in Fig. I.E.11 for both cases. In the case of the iron-rich central region, the only spatial variation in flux shape seems to be one of attenuation. This is because the composition of the central region of the core is not greatly different from that of the structural region. In the case of the nickel-rich central region, the fluxes at the center and at the interface show the effects of the high nickel concentration. However, the effects have disappeared at the center of the core, and fluxes in both cases are essentially the same.

j. Reactor-physics Calculation for Run 38 (62.5 MWt)
(L. B. Miller and R. E. Jarka)

A final configuration for operation at 62.5 MWt has been determined. Calculations with the DOT5 (two-dimensional DSN) code indicate that this configuration will have the same excess reactivity as

*Meneghetti, D., Rago, A. L., and Phillips, K. E., Use of the Elmoe-Snarg Programs to Study Details of Neutron Spectra through Regions of Resonance-Scattering Media, Resúmenes de los artículos Presentados en la Conferencia Internacional sobre Utilización de Reactores de Investigación y Computo y Mathematica de Reactores, Mexico City (1967).

the Run-32D configuration ($\sim 1/2\%$ k_{ex}). The calculations were performed in x-y geometry with each subassembly in the core described individually to consider fully the heterogeneity introduced by control rods, safety rods, and experimental subassemblies. The computed k_{eff} for the Run-38 configuration was compared with the k_{eff} for the Run-32D configuration computed by the same method to determine the reactivity of the Run-38 loading.

Fig. I.E.11. Neutron-flux Spectrum at Various Spatial Positions in an EBR-II Core with a Nickel-rich and with an Iron-rich Central Region

6. Driver Fuel Development (C. M. Walter)

a. High Burnup Encapsulated Irradiations

Last Reported: ANL-7595, pp. 64-67 (July 1969).

(i) Preliminary Information for Encapsulated Mark-II Elements Irradiated to ~4 at. % Burnup (R. V. Strain and W. N. Beck)

Sixteen encapsulated Mark-II elements from Subassembly XO53 have been nondestructively examined by neutron radiography. There were no indications of failure. Measurements of fuel-column length showed that the fuel was contacting the restrainers. Since selected elements from this subassembly that had been examined at 2 at. % burnup showed the identical condition, the restrainers evidently are effective in limiting axial growth of the fuel.

The plenums of six capsules were punctured; the recovered gas did not contain fission-product isotopes, thereby verifying that the claddings were intact. The diameters of four capsules increased from 0.4 to 0.5% and those of two elements increased from 0.5 to 0.6%. The close agreement of these diameter increases indicates that the increases resulted from swelling of the stainless steel rather than from jacket strain. The steel had been exposed to maximum fluences of 3×10^{22} nvt.

b. Fuel and Cladding Surveillance

Not previously reported.

(i) Irradiation of Mark-II Subassemblies (W. N. Beck and N. R. Grant)

Three subassemblies of unencapsulated Mark-II elements were inserted in the reactor at the beginning of Run 36. These elements have reached a calculated 0.6 at. % burnup. Interim examination of elements in one subassembly is scheduled to be performed at a calculated 2 at. % burnup.

7. Operation with Failed Fuel (R. R. Smith)

Last Reported: ANL-7595, p. 69 (July 1969).

a. Flat-topped TREAT Transient with a Partially Bonded Mark-IA EBR-II Fuel Element (R. M. Fryer)

To investigate the effects of residual bond sodium on melting phenomena in a Mark-IA EBR-II fuel element, a flat-topped TREAT

transient was conducted with a Mark-IA fuel element that contained only enough sodium to bond the lower half of the fuel pin. To simulate the loss of bond in the upper half of the fuel element as realistically as possible, the assembled test element was inverted (with the bond molten) and subsequently impacted.

The test specimen, enriched to 6 wt.% in ^{235}U , was subjected for approximately 7 sec to a flat-topped TREAT transient, during which the power density in the specimen corresponded to an EBR-II power level of 120 MWt.

After the transient was completed, the test element was removed from the loop, washed, and transferred to the air cell of the Fuel Cycle Facility. A visual examination revealed no external damage. A neutron radiograph of the test element while it was still in the loop and eddy-current bond measurements of the element indicate that the top of the fuel material is still at the original elevation. Based on this information, it is tentatively concluded that fuel-melting effects, if any, were small. More exhaustive postirradiation examinations will be conducted. These will include jacket profilometry, gamma scans, and metallographic examinations.

b. Studies with the Reactor Cover-gas Monitor (G. S. Brunson)

The EBR-II reactor cover-gas monitor (RCGM) detects rare-gas fission products in the reactor argon cover gas. It consists essentially of a single photomultiplier with a 2-in. x 2-in. sodium iodide crystal from which the signal is fed to three independent single-channel analyzers. Each channel feeds a count-rate meter having both logarithmic and linear outputs. The outputs are recorded by two three-pen recorders, one for the log signals and one for the linear signals, located in the EBR-II control room. Except for the recorders, the entire system is physically located in the depressed area in the reactor building. The detector head is furnished with a massive steel shield to reduce background; immediately adjacent to the crystal is a gas-counting volume of approximately 40 cm³ through which reactor cover gas (argon) is circulated. Rare-gas atoms that decay in the gas-counting volume produce characteristic gamma rays, which can be detected by the adjacent scintillation detector. In principle, each of the single-channel analyzers may be adjusted to count only those gamma rays originating from specific, significant fission-product species.

A comprehensive program has been undertaken to evaluate the RCGM and to qualify it as operational instrumentation. Accordingly, a Nuclear Data ND 120 multichannel pulse-height analyzer was installed to measure the gamma spectrum "seen" by the RCGM and to analyze the performance of the RCGM in counting selected bands from that spectrum. Normal operation with a clean core produces free fission products in the

coolant that correspond to the presence of a few milligrams of exposed ^{235}U on core components. This effect is stable and apparently irreducible. In the following discussion, the fission-product signal analyzed comes from this so-called "tramp" uranium.

Reactor operators had noted that the response of the instrument appeared in some way to be sensitive to changes in the bulk-sodium temperature. At first glance, this seemed unlikely to be a real effect. Furthermore, grab samples of cover gas did not reveal any temperature effect when counted on the gamma spectrometer in the Laboratory and Service Building. The inability to reconcile such conflicting information raised the question as to whether there was some inadvertent electronic effect in the RCGM system.

To resolve this conflict, the stability of the RCGM was tested first with an electronic pulse generator and then with a ^{203}Hg reference source. Its stability was entirely acceptable. The matter was further clarified when the RCGM photomultiplier head was removed from the counting position and the gamma activity in the counting volume was observed with the GM probe of an ordinary hand survey meter. While the bulk-sodium temperature was being increased at a rate of approximately $\frac{1}{2}^\circ\text{F}/\text{min}$ for about 20 min, the survey meter indicated a gross gamma level higher by a factor of two than the equilibrium level. When the bulk-sodium temperature was stabilized at the higher level, the gamma activity returned to the equilibrium level. Thus, as has also been observed with the RCGM itself, the increased gamma activity appeared to depend on the rate of temperature rise rather than on the temperature per se. So far no convincing effect has been observed for temperature decreases.

Another test involved shutting off the gas flow and observing the gross gamma decay with the hand survey meter. Initially the decay showed a half-life of the order of 0.5 min. This makes it clear why the results of grab-sample analyses were in conflict with those from the RCGM and demonstrate the lack of temperature dependence. Approximately 5 min are required to obtain a grab sample and to carry it to another building for counting; the short-lived activity decays during the delay.

As determined with the ND 120, the RCGM can identify the following gamma lines only (tentative identifications based on energy and half-life are noted):

<u>Energy (keV)</u>	<u>Isotope</u>	<u>Half-life</u>
81	^{133}Xe	5.27 days
150	$^{85\text{m}}\text{Kr}$	4.4 hr
250	^{135}Xe	9.2 hr
440	^{23}Ne	38 sec
1260	^{41}Ar	1.8 hr

The 1260-keV line listed for ^{41}Ar does not correspond exactly with information given in the literature, probably because of another gamma in the same vicinity. Except for the ^{23}Ne , which decays in transit, the above spectral lines have been confirmed by use of a high-resolution GeLi gamma spectrometer. About 10 other gamma lines were also identified. From clues found in the RCGM spectra, it appears that there are a substantial number of other lines originating in short-lived isotopes to be found in on-line counting with high-resolution equipment. All gammas presumably come from fission products, except for ^{23}Ne and ^{41}Ar , which are generated by neutron activations.

It seems clear that the transient temperature effects are associated with the ^{23}Ne , which comes from an n,p reaction with the primary sodium. Since the ^{23}Ne has a higher-energy gamma than have the first three isotopes listed in the table, any analyzer window adjusted to count one of those isotopes cannot avoid counting gammas from the Compton spectrum of ^{23}Ne . Short-term variations in the ^{23}Ne activity are astonishing; on one occasion, the counting rate in a matter of 2-3 min increased by a factor of nine. This effect is particularly noticeable during startups, when the bulk-sodium temperature fluctuates. For example, the reactor started up early on August 17 after a shutdown of about 70 hr. The ^{135}Xe and $^{85\text{m}}\text{Kr}$ concentrations had decayed to a very low level, and the ^{133}Xe concentration was about 70% of equilibrium. As the reactor power was raised to 10 MWt, the bulk-sodium temperature fluctuated 3-4°F. The three RCGM channels, each aligned on one of the above isotopes, rose by a factor of five above equilibrium level, subsided for 4 or 5 min, and then rose again to the same elevated level as the temperature again increased. As yet there is no plausible explanation as to why small changes in the bulk-sodium temperature should cause such unexpected variations in the rate of evolution of neon to the cover gas.

This phenomenon raises substantial questions as to how the RCGM can ever be used as a dependable indicator of fission-product activity in the cover gas. If the bulk-sodium temperature remains relatively constant, the RCGM indication of the xenon activities agrees well with the results of grab-sample data. However, the temperature varies substantially during startups, when the RCGM might perform its most valuable service in giving early warning of a failed experiment. It would be possible to introduce enough tubing in the system to provide 2 or 3 min of delay during which the ^{23}Ne could decay before the gas reached the RCGM. Under these circumstances, the RCGM should give results essentially duplicating those obtained with grab samples, but such a delay would largely vitiate its value as an on-line instrument.

A more advanced system could be built around a high-resolution GeLi detector. If equipped with an anticoincidence Compton screen, such a system would be able to detect the significant fission-product isotopes while

ignoring nonfission sources such as ^{23}Ne and ^{41}Ar . This kind of system would have other interesting capabilities. Because of its high resolution, it could provide a great deal of information from the cover-gas spectrum. The present RCGM sees only the five isotopes listed above, of which only the first three are significant in monitoring fission-product-gas activities. The high-resolution spectrometer would see perhaps 25 to 35 lines when operated on-line. From this abundant information, it might be possible to recognize the "fingerprints" of the material releasing fission products to the system. For example, the distribution of fission-product activities in a release might indicate whether the failure involved uranium or plutonium, and possibly the irradiation "age" of the failed element. Such a capability would be of enormous value for identifying leaking elements quickly so that they can be removed with a minimum of downtime.

One problem common to both systems is that of "fall out" of solid noble gas daughters in the gas-counting volume. This background, presumably β active, has a continuous spectrum when analyzed separately. A cut-and-try approach is to be used to determine how much of this can be filtered out without sacrificing too much of the signal from the ^{133}Xe .

Although the objective of the RCGM is to monitor the cover gas for fission products that would give warning of fuel failure in the reactor, the behavior of the ^{23}Ne should not be disregarded. The significance of this behavior remains to be seen; however, it is indeed startling to see a change in bulk-sodium temperature from, say, 700 to 702°F in a minute or two result in a ninefold increase in the release rate of the gas atoms to the cover gas. Such sensitivity may eventually be exploited to learn more about gaseous diffusion and solution phenomena in hot molten-sodium systems.

c.. Study of Cladding Failure of a Mark-IA Driver Element (P. B. Henault)

A series of controlled in situ experiments involving the irradiation of Mark-IA driver-fuel elements up to and beyond the point of cladding failure has been proposed. The primary objectives of the experiments are to establish the manner in which the cladding will fail as a result of excessively high burnup and to determine what would be the consequences to safe reactor operation, if any, if such a failure were to occur inadvertently. A secondary purpose is to help establish a realistic upper burnup limit for the Mark-IA fuel.

(i) Background. One of the important factors related to EBR-II plant performance today is concern for the possible consequences of fuel-element failure. Many of these consequences are based on hypothetical modes of failure that may or may not be credible or even possible.

Though concern for the consequences of anomalies of experimental fuel elements is and will continue to be a primary concern, the state of the art of Mark-IA driver fuel has now advanced to the point where concern for the "possible" consequences of this fuel experiencing anomalies may be discounted. At the least, a relaxation of this concern will permit extension of the present operating parameters and fuel-burnup limits to their optimum values.

From the information now compiled about the Mark-IA element, it is becoming apparent that cladding failure under the most severe conditions (i.e., as a result of excessively high burnup) should not jeopardize safe reactor operation. This conclusion is based on certain assumptions and data which, though subject to error, have a high degree of confidence.

To demonstrate conclusively the assertion that cladding failure will in no way endanger the reactor, the series of controlled experiments has been proposed.

(ii) Method of Performing Experiments. Initially, three experiments are planned for the series:

(1) Operation of a single unencapsulated fuel element in a modified EBR-II driver subassembly until the cladding fails in some manner.

(2) Operation of a modified driver subassembly containing a cluster of high-burnup elements until the cladding of one of the elements fails.

(3) Operation of one or more elements having experienced cladding failure as a result of excessively high burnup for some reasonable period of time after failure.

The first experiment is intended to demonstrate that the consequences of cladding failure will be minor and that adjacent elements will not be affected, and to determine behavior of the reactor system during fuel-element deterioration. The second is intended to demonstrate that the results of the first experiment were typical. The third is intended to determine if a defective driver element can remain in operation until it is convenient to remove it, probably during the next scheduled fuel-handling operation.

(iii) Description of First Experiment. Of the at least three experiments anticipated, only the first is specifically proposed at this time. A single Mark-IA element, previously operated to a relatively high burnup, is to be irradiated at the center of a modified EBR-II driver subassembly.

This "test specimen" will be surrounded by two rows of fresh fuel and a row of dummy stainless steel elements; the remainder of the subassembly

will be filled with fresh fuel. The row of 18 stainless steel elements will not significantly affect the temperature distribution and neutron flux "seen" by the test specimen, but will act as a barrier in the unlikely event that the cladding failure causes some adverse effects to adjacent elements. The proposed configuration is illustrated in Fig. I.E.12.

If cladding failure of the test specimen has not been indicated by the time the other elements reach their normal burnup limit, the subassembly holding it will be removed from operation, and the test specimen will be studied by nondestructive techniques. Then, the test specimen will be reinserted at the center of a new subassembly.

Fig. I.E.12. Loading Diagram for EBR-II Test Subassembly Containing the Irradiation-to-failure Specimen

Following definite indication of cladding failure, the reactor will be shut down, and all reactor parameters and other plant conditions will be

monitored to determine any adverse effects. The test subassembly then will be removed to the Fuel Cycle Facility, where it will be disassembled and examined exhaustively.

(iv) Possible Modes of Cladding Failure. The Mark-IA metallic fuel expands or swells during irradiation because of fission-product formation. A fraction of the fission gas is released and accumulates in the gas plenum. Initially, however, most of the gas remains trapped in the lattice structure of the fuel. As irradiation continues, fuel swelling causes sodium in an annulus between the fuel and cladding wall to be displaced upward into the plenum above the fuel. Eventually, the fuel will contact the cladding, and further fuel swelling will deform the cladding. This continued swelling will occur at a reduced rate because of the fuel-cladding contact pressure.

As the fission-gas inventory in the plenum region increases and as sodium is continuously displaced upward because of fuel swelling, the gas pressure in the plenum increases substantially. At high burnup levels, two forces act on the cladding surface: the internal gas pressure and the outward expansion of fuel. It is one of these forces that is expected to cause cladding failure. Five possible modes of failure are envisioned: (1) cladding fracture due to excessive fuel swelling, (2) cladding fracture

due to excessive internal gas pressure, (3) cracking or fracture of the top weld, (4) cracking or fracture of the bottom weld, and (5) cladding fracture due to buildup of bond-sodium pressure.

The five modes of failure are listed in the order of their probability; the last three are believed to have very low probability.

(v) Consequences of Cladding Fracture from Outward Pressure of Fuel Expansion. Analyses indicate that the main consequence of failure by this mode would be an approximate 10% rise in centerline fuel temperature as a result of the decreased thermal conductivity accompanying the increase in void fraction. Heat transfer is not lost during cladding failure, and the maximum fuel temperature never approaches the boiling temperature of sodium. The temperature of the fuel surface actually decreases because of the loss of thermal resistance as the fuel contacts the inside cladding surface. Table I.E.6 indicates the changes in fuel temperature at two different axial positions for varying degrees of fuel expansion.

TABLE I.E.6. Fuel Temperature in High-swelling Element in Position 4N2

	Fuel Temperatures (°F)		
	Centerline	Average	Edge
<u>At Axial Flux Peak</u>			
Fresh fuel (for reference)	1009	957	904
17% expansion	1059	947	888
30% expansion	1115	1000	884
<u>At Top of Fuel Pin</u>			
Fresh fuel	1069	1033	997
17% expansion	1096	1041	986
30% expansion	1132	1058	983

Surprisingly, the calculated value of fuel-surface temperature is decreased even further by consideration of the coolant flow adjacent to the test element. As the fuel jacket swells, the distance between the center of the element and the outside of the spiral wrapper wire increases, thereby forcing the adjacent elements radially outward and away from the test element. This effect is not insignificant; flow can actually increase by as much as 7%.

(vi) Consequence of Cladding Failure from Excessive Internal Gas Pressure. The second most probable mode of cladding failure is considered to be a fracture in the upper cladding region resulting from excessive internal gas pressure. The uncertainties in the calculated gas

volume make it impossible to estimate accurately the internal gas pressure at high burnup levels. Between 2.5 and 3.0 at. % burnup, however, the pressure probably rises above 5000 psi. From static-pressure-bursting theory, it was calculated that the internal gas pressure necessary to cause cladding fracture of a Mark-IA element would be of the order of 6500 psi.

Assuming that the expanding gas could blanket the outside cladding surface for a finite time as it escaped, the resultant reduction in heat transfer was considered. Both the extent of flow reduction that could be tolerated and the extent of circumferential surface that could be completely and continuously insulated

Fig. I.E.13. Extent of Coolant-channel Blockage by Released Fission Gas That Can Be Tolerated without Causing Temperature to Rise to Fuel-cladding Eutectic Point of 1340°F

before the fuel temperature rises above the fuel-cladding eutectic point were calculated. The results indicated that, for the most likely case, a flow reduction of 50% or an insulated circumferential surface area of 140° of arc could be tolerated. Further calculations indicated that, for the worst case, all escaping gas would be carried away in less than 60 msec. Figure I.E.13 indicates the amount of surface that could be continuously blanketed by gas without a resultant cladding failure. Table I.E.7 shows the magnitude of blanketing that could be tolerated for a number of specific cases.

TABLE I.E.7. Circumferential Fuel-element Surface Which Can Be Completely Insulated under Steady-state Operating Conditions before Fuel Temperature Exceeds Fuel-cladding Eutectic Temperature

Axial Location on Element	Fuel Expansion $\Delta V/V$ (%)	Degrees of Arc
Near top	0	210
Near top	17	160
Near top	30	130
Axial flux peak	0	190
Axial flux peak	17	140
Axial flux peak	30	110

Flow reduction due to fuel extrusion or cladding movement into the coolant channel was also considered. The consequences of these events were found to be less severe than the consequences resulting from gas release.

Effects on the adjacent fuel elements occurring from the release of stored energy were considered. It was shown that temporary deflection but no permanent displacement would occur.

(vii) Consequences of Other Modes of Failure. The consequences of the other three credible modes of failure were investigated. In each case, the possible consequences were found to be less severe than those discussed above.

Review of all credible modes of cladding failure reveals that the consequences, if detectable, will not be severe. A small flow reduction caused by escaping gas or by fuel extrusion or cladding displacement into the coolant channel is probably the most serious of the conceivable consequences. In no way is it considered possible for measurable damage to adjacent elements to occur.

(viii) Failure Detection. Failure detection is the most uncertain part of the experiment. All the normal fission-product and delayed-neutron monitoring techniques will be employed in the hope of detecting the failure shortly after it occurs. Actual detection will depend on the particular mode of cladding failure as well as the rate and magnitude. From consideration of all the possibilities, it appears that detection may be done by none, any one, or any combination of the possible techniques. The signals and indications considered most probable are summarized in Table I.E.8.

TABLE I.E.8. Probable and Possible Signals Indicating Cladding Failure of Mark-IA Element in EBR-II

Mode of Failure	Most-probable Response	Possible Response
Fracture of top weld	Clear signal increase on the fission gas monitor (FGM) and the reactor cover gas monitor (RCGM).	No other signal likely.
Fracture of bottom weld	Gradual increase in cover-gas activity due to decay of iodine escaping with bond sodium.	Response of fuel element rupture detector (FERD), FGM, and RCGM possible but not likely because swollen fuel pressing against cladding wall should prevent clear escape path. Also possible that failure may not be detected during reactor operation.
Excessive fuel expansion resulting in cladding fracture	Gradual increase in cover-gas activity from additional iodine species entering coolant.	Possible FERD, FGM, and RCGM response if free path exists for sodium and gas to escape. No response also likely.
Excessive internal gas pressure resulting in cladding fracture	Large response on the FGM and RCGM.	Possible FERD response, but unlikely.
Cladding fracture resulting from buildup of bond-sodium pressure	Gradual increase in cover-gas activity possible.	No other signal likely since failure by this mode presupposes a tight seal between the fracture and the gas and sodium in the element plenum.

F. EBR-II--Operations

1. Reactor Plant (G. E. Deegan)

Last Reported: ANL-7595, pp. 69-70 (July 1969).

The reactor was operated for 1120 MWd, in Runs 36A, 36B, and 37, from July 21 through August 20. The cumulated total of EBR-II operation is 28,194 MWd.

Before the end of Run 36A, the reactor scrambled because of indicated fast periods on nuclear channels 4, 5, and 6. Analysis of available data, including a reactivity-meter recording, failed to confirm actual parameter changes. A power-supply perturbation was considered to be the most likely cause of the scram, and a special recorder was installed to monitor the voltage of the nuclear-continuous-power supply. There was no indication of anomalous reactor behavior on restart.

Early in Run 36B, failure of one of the sight-glass segments of the steam drum necessitated a manual reactor scram. After the sight glass was isolated, reactor power was returned to 50 MWt. All mica strips in both steam-drum sight glasses were replaced. There were no further interruptions of Run 36, which was completed on July 31.

The reactor was started up for Run 37 on August 2. Rod-drop experiments were performed at 50 MWt and 500 kWt. Steady-power operation then continued until August 14, when a voltage dip on the National Reactor Testing Station 138-kV line caused the line breakers to open in the incoming line. Multiple false scram annunciations and off-normal indications resulted from the voltage perturbations, and the reactor was manually scrambled. Normal power and also nuclear and process continuous power were lost temporarily. The plant was placed in standby while the event was evaluated. It was determined that low battery voltage had caused the loss of continuous power at the time of the scram. The batteries were charged, load tested, and recharged. Fifty-megawatt (thermal) operation was resumed, and Run 37 is continuing at that power level.

Loading changes for Runs 36B and 37 included the following:*

For Run 36B, one controlled-flow subassembly and one extended-burnup subassembly that had completed their planned irradiation were removed from the grid, and a controlled-flow subassembly and a subassembly containing vendor fuel elements, both with previous irradiation, were installed. The vendor-fuel subassembly contains fuel elements made by the vendor but bonded by ANL.

*Loading changes involving experimental subassemblies are described in Sect. I.E.2.a.

For Run 37, the last 70%-enriched subassembly, five high-silicon extended-burnup subassemblies, four subassemblies containing vendor fuel, one low-silicon extended-burnup subassembly, three structural experiments, and two fueled experiments were removed from the grid. The following subassemblies were installed: one containing previously irradiated vendor fuel elements; one containing fresh vendor fuel elements heat treated by ANL;* one containing fresh ANL cold-line elements bonded by the vendor; the test subassembly containing a known upper-weld defect (which had been removed from the grid after Run 34B); and a subassembly containing samples in the upper shield section for carbon-equilibration measurements.

2. Fuel Cycle Facility (M. J. Feldman)

Last Reported: ANL-7595, pp. 70-76 (July 1969).

a. Fuel (D. L. Mitchell)

(i) Cold-line Production and Assembly. Table I.F.1 summarizes the production activities for July 16 through August 15, 1969, and for the year to date.

TABLE I.F.1. Production Summary for FCF Cold Line

	7/16/69 through 8/15/69		Total This Year	
	Mark IA	Mark II	Mark IA	Mark II
Alloy-preparation runs				
New fuel	3	0	7	8
Remelts	5	0	10	3
Total	8	0	17	11
Injection-casting runs	9	0	25	10
Pins processed				
Accepted	923	0	2,515	941
Rejected	40	0	86	53
Elements welded	929	0	2,940	884
Elements rewelded	0	0	0	69 ^a
Elements leaktested				
Accepted	820	0	2,622	804
Rejected	10	0	50	21
Elements bondtested				
Accepted	652	0	2,468	934
Rejected	13	0	286	9
Subassemblies fabricated (cold-line fuel)	4	0	19	6
Elements received from vendor	200		24,088 ^b	
Inspected and accepted	200		23,407 ^{b,c}	
Inspected and rejected	0		1,240 ^b	
Subassemblies fabricated (vendor fuel)	1 ^d		9 ^e	
Total elements available for subassembly fabrication as of 8/15/69				
Cold-line fuel				
Mark IA	1,223			
Mark II	234			
Vendor fuel (Mark IA)	22,394			

^aIncludes 64 elements in which visual examination of welds indicated that they were not acceptable for potentially high-burnup experiments.

^bTotal includes figures for 1968.

^cIncludes fuel elements returned to vendor for rework to correct voids in sodium bond and after rework sent back to ANL for reinspection.

^dEach subassembly is made up of a mixture of vendor and cold-line fuel elements.

^eIncludes subassemblies made up of a mixture of vendor and cold-line fuel elements.

*As part of a separate effort, this subassembly also contains melt wires (to monitor outlet temperatures) and porous silicon carbide samples (to determine temperatures by radiation-induced changes).

Ten ingots have been received from Aerojet-General Corporation (AGC) and are being used to injection-cast fuel pins. Bonding of 2200 unbonded fuel elements currently being received from AGC has been started.

Four Mark-IA subassemblies were fabricated in the cold line during the month.

(ii) Inspection of Vendor Fuel. A summary of the data relating to receipt and acceptance of the fuel produced by AGC is included in Table I.F.1.

Inspection of all AGC-fabricated elements available at ANL has been completed. Inspected this month were 200 elements that had been previously rejected by ANL, subsequently reworked by AGC, and then returned to ANL for reinspection. All were accepted.

b. Surveillance (M. J. Feldman, J. P. Bacca, and E. R. Ebersole)

(i) Postirradiation Analysis of EBR-II Fuel (J. P. Bacca)

(a) Surveillance of Vendor-produced Fuel

(1) Fuel-characterization Studies. Several laboratories have been characterizing irradiated and unirradiated driver fuel produced by AGC. These efforts are being phased out at Los Alamos Scientific Laboratory and Pacific Northwest Laboratory, but are being continued at the Savannah River Laboratory (SRL) and ANL. The X-ray investigations being conducted at SRL are especially significant because they relate directly to the determination of preferred orientation in the fuel, which is hypothesized to be a key factor in the anomalous irradiation performance of the AGC fuel.

(2) Postirradiation Examination. Metallographic examinations of AGC fuel are essentially complete. No observations of further significance resulted from this work. Gamma scanning of irradiated AGC elements has been discontinued as a means to detect by nondestructive means if the diameters of the AGC fuel pins have increased at the top end rather than at the bottom end of the elements. Density determinations also are essentially complete.

(3) Irradiation Experiments. Table I.F.2. summarizes the status of driver subassemblies that are being irradiated or are ready for postirradiation examination in the effort to characterize the performance of AGC fuel in EBR-II.

TABLE I.F.2. Status of Driver Subassemblies in Which the Performance of AGC Fuel Is Being Characterized

Subassembly No.	Remarks
C-2200	Contains fuel cast by AGC and impact bonded by ANL. Burnup of 0.76 at. % was achieved by the end of Run 36. The subassembly is now ready for postirradiation examination. Subassembly C-2200 is a companion to Subassembly C-2196 examined earlier (and reported last month) following irradiation to 0.35 at. % during Run 35.
C-2199	Companion subassembly to Subassemblies C-2196 and C-2200. Irradiation to 1.5 at. % is scheduled to be achieved during Run 39.
C-2209	Contains AGC fuel that was heat treated before centrifugal bonding in an attempt to prevent preferred orientation in the fuel during the bonding operation. The subassembly attained a burnup of 0.35 at. % during Run 36 and is ready for postirradiation examination.
C-2208	Contains ANL impact-bonded AGC fuel and AGC centrifugally bonded AGC fuel for which are known the radial positions of the pins in the injection-casting array and the "top-bottom" orientations of the pin castings in their jacket assemblies. The subassembly attained a burnup of 0.38 at. % during Run 36 and is ready for postirradiation examination.
C-2195	Contains as-fabricated AGC fuel irradiated to 0.35 at. % during Run 36; now available for postirradiation examination.
C-2182	Contains as-fabricated AGC fuel. Irradiation of the subassembly to a burnup of 0.88 at. % by the end of Run 37 is underway.
C-2211	Contains as-fabricated AGC fuel elements that have had a post-bonding "reclamation" heat treatment by ANL. This treatment, intended to remove inherent preferred orientation in the fuel, consisted of holding the elements at 660°C for 1½ hr followed by a 2-hr heat treatment at 500°C. The normal impact-bonding sequence was carried out during the 500°C heat treatment. Irradiation of the subassembly to approximately 0.39 at. % by the end of Run 37 should be achieved.
C-2210	Contains ANL-produced pins that were centrifugally bonded by AGC. This experiment should confirm or disprove the hypothesis that the dimensional instability of driver fuel is caused by the centrifugal-bonding operation. Irradiation of this subassembly to approximately 0.38 at. % by the end of Run 37 should be achieved.

(b) 70%-enriched Fuel Experiment. The last of the current series of 70%-enriched fuel subassemblies (C-2184S) attained a calculated peak burnup of 1.75 at. % by the end of Run 36. Postirradiation examinations of this subassembly will be initiated soon.

(c) Controlled-flow Experiment. Postirradiation examinations were made of the elements from the third controlled-flow subassembly (C-2187S), which had been irradiated to a peak burnup of 1.5 at. % by the end of Run 36A. The examinations indicated that the fuel in the Mark-IA elements had swollen 7.8 to 17.1% (see Table I.F.3) and that the fuel pins in

some of the elements had swollen to intimate contact with the internal diameter of the cladding tubing. The fuel pins in the Mark-IB elements had swollen more than the pins in the Mark-IA elements; swelling of the Mark-IB pins ranged from 12.0 to 21.0%. This higher swelling is apparently due to the larger gas-plenum volume of the Mark-IB element. Because of the larger volume, less gas pressure is generated in the element as the fuel pin swells. Therefore, the resistance to swelling is less in the Mark-IB element than in the Mark-IA.

TABLE I.F.3. Fabrication and Irradiation Data for Controlled-flow Driver-fuel Subassembly C-2187S

(Calculated burnup: 1.50 at. % max; 1.32 at. % avg)

Injection-casting Batch No.	Silicon Content of Fuel (ppm)	Number of Elements	Element- burnup Range (at. %)	Total Volume Swelling of Fuel ($\Delta V/V$, %)	
				Average	Range
<u>Mark IA</u>					
095 II	290	8	1.43-1.49	14.8	13.1-16.6
096 II	308	10	1.43-1.50	14.5	11.8-15.9
097 II	276	10	1.45-1.49	15.6	13.7-17.1
098 II	289	16	1.43-1.50	14.9	7.8-17.1
<u>Mark IB</u>					
095 II	290	8	1.43-1.49	17.0	14.3-18.7
096 II	308	10	1.43-1.49	16.1	12.0-20.6
097 II	276	9	1.44-1.50	17.0	13.4-20.7
098 II	289	17	1.43-1.50	17.7	13.7-21.0

Precision diameter surveys of selected elements were made to determine whether or not cladding straining took place. These data have not been analyzed.

Three controlled-flow subassemblies (C-2188S, C-2197S, and C-2198S) are being irradiated in the EBR-II core.

(d) Driver-fuel Extended-burnup Program. Beginning with Run 37, the maximum allowable burnup for EBR-II driver fuel was increased from 1.2 to 1.5 at. %. Additional postirradiation data supporting this increase were obtained from additional surveillance subassemblies irradiated to approximately 1.5 at. %. These data are summarized for subassemblies C-2104, C-2107, C-2071, and C-2101 in Tables I.F.4 through I.F.7. The swelling results were satisfactory and much as expected from previous results.

TABLE I.F.4. Fabrication and Irradiation Data for Extended-burnup
Driver-fuel Subassembly C-2104

(Calculated burnup: 1.51 at. % max; 1.26 at. % avg)

Injection-casting Batch No.	Silicon Content of Fuel (ppm)	Number of Elements	Element- burnup Range (at. %)	Total Volume Swelling of Fuel ($\Delta V/V$, %)	
				Average	Range
0446	160	1	1.43	8.07	-
4225	568	2	1.39-1.40	6.04	5.9-6.2
4227	222	23	1.37-1.49	6.20	5.2-7.7
4228	504	40	1.38-1.50	6.03	5.0-7.2
4229	200	25	1.38-1.47	6.13	4.9-6.8

TABLE I.F.5. Fabrication and Irradiation Data for Extended-burnup
Driver-fuel Subassembly C-2107

(Calculated burnup: 1.50 at. % max; 1.26 at. % avg)

Injection-casting Batch No.	Silicon Content of Fuel (ppm)	Number of Elements	Element- burnup Range (at. %)	Total Volume Swelling of Fuel ($\Delta V/V$, %)	
				Average	Range
0447	165	1	1.43	6.77	-
4228	504	3	1.44-1.45	6.28	5.9-6.5
4229	200	31	1.44-1.47	6.42	5.3-7.4
4230	350	30	1.41-1.47	6.02	5.0-7.2
4231	300	26	1.40-1.42	6.34	5.5-7.3

TABLE I.F.6. Fabrication and Irradiation Data for Extended-burnup
Driver-fuel Subassembly C-2071

(Calculated burnup: 1.51 at. % max; 1.28 at. % avg)

Injection-casting Batch No.	Silicon Content of Fuel (ppm)	Number of Elements	Element- burnup Range (at. %)	Total Volume Swelling of Fuel ($\Delta V/V$, %)	
				Average	Range
0410	101	50	1.37-1.49	16.17	14.3-21.4
0411	123	10	1.39-1.43	15.58	14.6-16.1
4211	272	31	1.40-1.46	8.31	6.8-10.6

TABLE I.F.7. Fabrication and Irradiation Data for Extended-burnup
Driver-fuel Subassembly C-2101

(Calculated burnup: 1.52 at. % max; 1.28 at. % avg)

Injection-casting Batch No.	Silicon Content of Fuel (ppm)	Number of Elements	Element- burnup Range (at. %)	Total Volume Swelling of Fuel ($\Delta V/V$, %)	
				Average	Range
0442	90	1	1.45	15.80	-
4225	568	35	1.39-1.51	6.29	5.3-7.4
4226	318	48	1.39-1.51	6.36	5.2-8.4

In the continued effort to increase the burnup limitation further, postirradiation examinations were made of two subassemblies (B-3029 and C-2073) after irradiation to burnup levels greater than 1.5 at. %. Examination results for the two subassemblies are summarized in Tables I.F.8 and I.F.9. Data from precision diameter surveys of selected elements from the subassemblies are being analyzed.

TABLE I.F.8. Fabrication and Irradiation Data for Extended-burnup
Driver-fuel Subassembly B-3029

(Calculated burnup: 1.66 at. % max; 1.32 at. % avg)

Injection-casting Batch No.	Silicon Content of Fuel (ppm)	Number of Elements	Element- burnup Range (at. %)	Total Volume Swelling of Fuel ($\Delta V/V$, %)	
				Average	Range
058 IH	340	19	1.47-1.59	6.9	5.2-10.1
059 IH	406	72	1.45-1.65	6.5	4.5-8.1

TABLE I.F.9. Fabrication and Irradiation Data for Extended-burnup
Driver-fuel Subassembly C-2073

(Calculated burnup: 1.75 at. % max; 1.46 at. % avg)

Injection-casting Batch No.	Silicon Content of Fuel (ppm)	Number of Elements	Element- burnup Range (at. %)	Total Volume Swelling of Fuel ($\Delta V/V$, %)	
				Average	Range
4212	260	14	1.66-1.73	12.09	9.1-15.0
4213	430	65	1.59-1.73	7.04	4.8-8.8
4214	340	12	1.59-1.69	6.77	5.7-8.1

Subassembly C-2169 attained a calculated peak burnup of 1.88 at. % by the end of Run 36. Postirradiation examination of elements from this subassembly is under way. Driver Subassembly B-3038, being irradiated in the reactor, should attain a peak burnup of 1.97 at.% by the end of Run 37.

(e) Mark-II Encapsulated-element Subassemblies
(J. P. Bacca and R. V. Strain)

Metallographic examination of three encapsulated Mark-II elements (Nos. 201, 212, and 251)* from experimental Subassembly XO29 revealed that several changes had occurred in the fuel and cladding during residence in EBR-II. These changes were as follows:

- (1) The fuel pins had swelled out to or very near the cladding along the entire length below the restrainer in each element. This observation confirms the ~35% swelling that was calculated for these fuel pins from the changes in the sodium levels of the elements.
- (2) Voids that were optically resolvable at 600X were observed above the midlength and at the edges of the fuel pins. The location of the voids indicates that the greatest amount of swelling occurred in the unrestrained and highest temperature regions of the fuel pins.
- (3) There was an interaction between the fuel pin and cladding at the midlength of Elements 201 and 212 and at both the midlength and top of Element 251. Electron-microprobe analysis of the interaction zone indicates that the interaction was mechanical rather than chemical. Some of the other observations made in this study tend to corroborate this hypothesis.
- (4) The cladding at the midlength and top of the elements was sensitized, but the cladding at the bottom end of the elements was not. This variation in sensitization of the cladding is normal for Mark-IA elements and reflects the dependence of the degree of sensitization on temperature.
- (5) The outside diameter of the cladding of Element 212 exhibited evidence of corrosion at the grain boundaries. The appearance of this attack at the grain boundaries indicates that the attack was chemical, but there is a possibility that the defects existed in the as-received tubing.

*Maximum at. % burnups attained by the elements were: Element 201, 1.82; 212, 2.14; and 251, 2.14.

(f) Effects of Sodium and Sodium Removal on the Microstructure of Type 304L Stainless Steel Tubing
(J. P. Bacca and R. V. Strain)

Type 304L stainless steel tubing is employed as the cladding and encapsulated material for the driver fuel and most experimental capsules in EBR-II. In EBR-II, the outside surface of the elements and capsules is exposed to flowing sodium at temperatures from 700 to 1100°F. The sodium clinging to these surfaces must be removed before the subassembly is exposed to air for interim or postirradiation examination. In the removal operation, the sodium is oxidized to sodium oxide and sodium hydroxide with humidified argon and air. These oxidation products then are removed from the surfaces of the elements and capsules by flowing water through the subassembly.

To determine the effect, if any, of the reactor primary sodium and the sodium-removal operation on the microstructure of cladding and encapsulation materials, a number of samples from elements and capsules which had been in the reactor and through the sodium-removal operation were examined metallographically. To date, these examinations have revealed no changes which could be attributed to either the reactor sodium or the sodium-removal operation. The microstructural change that has been observed is sensitization (carbide precipitation at the grain boundaries), which is dependent on the temperature of the cladding during reactor operation and on the original carbon content of the material.

c. Fuel Handling and Transfer (N. R. Grant and P. Fineman)

Table I.F.10 summarizes fuel-handling operations during the month.

d. Experimental Support (V. G. Eschen and N. R. Grant)

Examination of Subassembly XO40 is complete, and the data are being analyzed. A solid stainless steel dummy element will be substituted for one element (012) that showed a possible scratch on the cladding surface. Element 012 will be destructively examined. No other significant abnormalities were noted.

Subassembly XA08, containing 8 mixed-carbide fuel capsules and 11 materials capsules, was received from the reactor and dismantled. It was installed in the reactor in December 1965 and had obtained a calculated maximum burnup of 10.5 at. %. Examination showed that the dimensions of the hexagonal tube across the flats were 0.042 to 0.056 in. larger than the nominal dimension of 2.290 in. Two opposite corners of the lower half of the tube were slit to facilitate removal of the tube from the fuel bundle. All of the fueled capsules have been returned to the experimenters.

TABLE I.F.10. Summary of FCF Fuel Handling

	7/16/69 through 8/15/69	Total This Year
<u>Subassembly Handling</u>		
Subassemblies received from reactor		
Driver fuel (all types)	14	85
Experimental	5	15
Other (blanket)	2	4
Subassemblies dismantled for surveillance, examination, or shipment to experimenter		
Driver fuel	17	91
Experimental	5	15
Other (blanket)	0	2
Driver fuel elements to surveillance	982	4379
Number from subassemblies	17	91
Subassemblies transferred to reactor		
Driver fuel	5	48
Experimental	0	5
<u>Fuel-alloy and Waste Shipments</u>		
Cans to burial ground	4	20
Skull oxide and glass scrap to ICPP	0	2
Recoverable fuel alloy to ICPP		
Fuel elements	6 (103.97 kg of alloy)	26 (434.67 kg of alloy)
Subassemblies	0	4 (20.4 kg of alloy)
Nonspecification material	0	5 (84.3 kg of alloy)

Subassembly XO34, containing seven ORNL structural capsules, was dismantled, and three of the capsules were returned to the experimenter.

Subassembly XO65, containing pressurized capsules for ANL inpile creep studies, was dismantled. The capsules are being measured.

Subassembly XO67, containing seven structural capsules, was dismantled, and the capsules were returned to the experimenters (PNL, ORNL, and GE).

PUBLICATIONS

Fission Process Phenomena Observed with Solid-State Track Recorders

R. J. Armani, R. Gold, and J. H. Roberts*

Abstracts of Papers Presented at the 158th Am. Chem. Soc. Mtg.,
New York, September 8-12, 1969, NUCL-41

Cosmic Radiation and Evolution: A Lunar Experimental Test

R. Gold

Radiation Effects 1(3), 173-175 (July 1969)

*Northwestern University.

The Attack on the Cladding of EBR-II Driver Fuel Element C-249-16

W. E. Ruther, T. D. Claar, and S. Matras

ANL-7537 (March 1969)

Postirradiation Inspection of Subassemblies Discharged from Runs 25 and 26 in EBR-II

R. R. Smith

ANL/EBR-002* (March 1969)

Locating and Identifying the Source of the May 24, 1967 Fission-product Release in EBR-II

R. R. Smith, D. W. Cissel, C. B. Doe, E. R. Ebersole, and F. S. Kirn

ANL-7543 (April 1969)

Analysis of Magnetic Fields in a Metal

D. L. Waidelich**

ANL-7551 (May 1969)

The following appeared in Proc. Intern. Conf. on Sodium Technology and Large Fast Reactor Design, Argonne National Laboratory, November 7-9, 1968. ANL-7520

Operating Experience with EBR-II

G. E. Deegan, F. S. Kirn, Harry Lawroski, and Robert Neidner

Part II, pp. 24-38

Introductory Remarks on the 1000-MWe LMFBR Follow-on Study Program

L. W. Fromm

Part II, pp. 169-170

Trace Element Behavior in Sodium

R. J. Meyer, C. E. Johnson, and L. E. Ross

Part I, pp. 291-294

Sodium Sampling and Analytical Experience at EBR-II

C. C. Miles, E. R. Ebersole, and W. H. Olson

Part I, pp. 213-221

Impurities in EBR-II Sodium and Cover Gas

W. H. Olson, C. C. Miles, and D. W. Cissel

Part I, pp. 222-226

The Corrosion of Vanadium and Vanadium-base Alloys in Sodium

W. E. Ruther

Part I, pp. 182-191

Water Cleaning and Air Storage Effects on Sodium-exposed Fuel Clad Alloys, 304 and 304L Stainless Steel

F. A. Smith, E. L. Kimont, and L. H. Bohne

Part I, pp. 426-437

*ANL/EBR-002 is the second of a series of "blueback" topical reports to be prepared by the EBR-II Project. These will be on file in all ANL libraries.

**University of Missouri.

Calculated Hydrogen-Oxygen Equilibria in Liquid Sodium

Peter Vilinskas

Part I, pp. 477-480

The following appeared in Trans. Am. Nucl. Soc. 12(Suppl.) (Oct 1969) as Abstracts

Safety Considerations for Plutonium Fuel Operation for ZPR-6 and -9

W. Y. Kato, L. R. Dates, G. K. Rusch, and K. E. Plumlee

p. 27

EBR-II as an Experimental Fast Reactor Test Facility

F. S. Kirn and J. F. Koenig

p. 49

Recent EBR-II Operating Experience

Harry Lawroski

p. 47

The Contribution of Fuel Expansion to the EBR-II Power Coefficient

J. K. Long

p. 48

ZPPR Start-Up and Operating Experience

R. G. Matlock, P. I. Amundson, R. E. Kaiser, J. C. Young,

R. O. Vosburgh, J. M. Gasidlo, and R. J. Forrester

p. 46

EBR-II Experimental Irradiation Experience

G. K. Whitham and D. W. Cissel

p. 49

II. OTHER FAST REACTORS--OTHER FAST BREEDER REACTORS--FUEL DEVELOPMENT

A. Irradiation Effects, Mechanical Properties and Fabrication

1. Irradiation Studies of Cladding Alloys

a. Effects of Irradiation on Type 304 Stainless Steel (R. Carlander)

Last Reported: ANL-7577, pp. 125-126 (April-May 1969).

The effects of irradiation at relatively low temperatures on the microstructure and on the mechanical properties are being investigated by tensile tests on stainless steel specimens taken from an EBR-II control rod, an experimental subassembly, and a safety rod. The specimens were irradiated between 371 and 463°C to fluences as high as $(9 \pm 0.9) \times 10^{22}$ n/cm². The effects of irradiation at higher temperatures are being investigated by tensile tests of specimens irradiated over a range of fluences in EBR-II experimental capsules at temperatures from ~450 to 650°C.

The effects of low-temperature irradiation on the tensile properties of Type 304 stainless steel at 450 and 550°C are illustrated in Figs. II.A.1 and II.A.2. The data are from recent tensile tests and from previous tensile tests performed on specimens from an EBR-II safety rod (see also Progress Report for March 1969, ANL-7561, pp. 58-60). The fluences given in the figures are total integrated neutron exposures and have been revised from those last reported in accordance with fluence determinations by the EBR-II Project.

Fig. II.A.1. Effect of Irradiation on the Tensile Properties of Type 304 Stainless Steel Irradiated between 371 and 460°C, and Tested at 450°C

Fig. II.A.2. Effect of Irradiation on the Tensile Properties of Type 304 Stainless Steel Irradiated between 371 and 460°C, and Tested at 550°C

The strength of the stainless steel increased rapidly as a result of irradiation between 1×10^{21} and $(1-2) \times 10^{22}$ n/cm². The ductility, as represented by the uniform and the total strains, decreased in a similar manner. When the stainless steel was irradiated to fluences above $(1-2) \times 10^{22}$ n/cm², the yield stress appeared to saturate at ~90,000 psi for a test temperature of 450°C, and at ~75,000 psi for a test temperature of 550°C. The minimum uniform strains at high fluences were 2 and 1.5%, respectively, at 450 and 550°C.

Since the microstructure of the irradiated stainless steel from the EBR-II safety rod has not been fully analyzed, neither qualitative nor quantitative relationships between the microstructure and the postirradiation tensile properties have been developed. An insight into the relation between microstructure and tensile properties may be gained, however, from the results of the microstructural examination of the Type 304 stainless steel from EBR-II control rod No. 12, which was irradiated in the same temperature range but to a lower fluence.* The examination showed that the irradiation produced a microstructure consisting of a homogeneous distribution of Frank dislocation loops and of polyhedral voids. The density of loops could not be determined quantitatively, but appeared to be higher both at lower irradiation temperatures and at higher fluences. The rapid increase in yield stress between 1×10^{21} and $(1-2) \times 10^{22}$ n/cm² at a test temperature of 450°C could be due to increase in the densities of either dislocation loops or voids (see Fig. II.A.1) or both. The deformation mechanism in this temperature range is not known, but is probably a nondiffusion-controlled process. The indicated saturation of the yield stress at high fluences may be due to a change from the deformation mechanism that operates at lower fluences. Dislocation channeling has been suggested as one of a number of processes operating in the high fluence range. The lower saturation value of yield stress at 550°C compared with 450°C may be due to annealing of the dislocation loops during the high-temperature test. This suggestion is supported by the results of postirradiation annealing of Type 304 stainless steel by workers at PNL. Their experiments indicated that removal of loops from the stainless steel matrix occurred near temperatures of 550-660°C.**

The preliminary results on the effects of high-temperature irradiation on the true yield stress and on true total strain of Type 304 stainless steel are given in Table II.A.1. The specimens for these tensile tests were selected from experimental irradiation capsules from EBR-II Subassembly XO16. The determination of the fluence level of the specimens is not complete; the irradiation temperature, as estimated from Tempil pellets, was between 427 and 593°C. The fluences given in the table were calculated with the assumption of a fast-neutron flux of 1.8×10^{15} n/cm²-sec (total) for the position of the subassembly in the reactor. The temperatures

*Carlander, R., Harkness, S. D., and Yaggee, F. L., Fast Neutron Effects on Type-304 Stainless Steel, Nucl. Appl. 7(1), 67-75 (July 1969).

**Quarterly Progress Report, Irradiation Effects on Reactor Structural Materials, BNWL-532, p. 12.51 (Aug. 15, 1967).

were also calculated based on the axial flux distribution at the subassembly location and a gamma heating value of 3 W/g. The tests were conducted at a strain rate of $1\% \text{ min}^{-1}$ at temperatures near those experienced by the specimens during irradiation.

TABLE II.A.1. Tensile Properties of Irradiated Type 304 Stainless Steel from Subassembly XO16

Total Fluence (n/cm^2)	Irradiation Temperature ($^{\circ}\text{C}$)	Test Temperature ($^{\circ}\text{C}$)	True Yield Stress (ksi)	True Total Strain
7×10^{21}	460	450	86.6	0.072
8×10^{21}	500	500	66.8	0.148
1.1×10^{22}	540	550	60.0	0.122
1.4×10^{22}	570	550	54.9	0.148
1.5×10^{22}	575	550	54.1	0.138

Lower irradiation temperatures resulted in higher yield stresses and lower total strains than did higher irradiation temperatures. A specimen irradiated to $7 \times 10^{21} \text{ n/cm}^2$ at 460°C , for example, had a total strain of 0.072, compared with 0.148 for a specimen irradiated to approximately the same fluence but at a temperature of 500°C (see Table II.A.1). In addition, the total strain of specimens irradiated to a higher fluence of from 1.1 to $1.5 \times 10^{22} \text{ n/cm}^2$ at temperatures between 540 and 575°C was twice as high as that of the specimen irradiated at the lower temperature and to a lower fluence.

One untested, high-fluence specimen of Type 304 stainless steel from Subassembly XO16 was examined by transmission electron microscopy. The examination showed some dislocation loops and voids in the matrix. Qualitatively, the density of the dislocation loops and the extent of void formation were less than observed in the Type 304 stainless steel control-rod specimens irradiated to approximately the same fluence. The lower densities of both loops and voids in specimens irradiated at 575°C could account for the lower yield strengths after irradiation compared with specimens irradiated at 371 - 463°C .

B. Coolant Effects on Cladding Alloys

1. Carburization and Localized Attack of Stainless Steel (J. Y. N. Wang and K. G. Figlik)

Last Reported: ANL-7553, pp. 71-73 (Feb 1969).

As previously reported, a long-term corrosion test was conducted with Types 304, 304L, 316, and 316L stainless steel. The exposure phase

of this test has been completed, and the conditions of the materials after 90, 180, 270, and 360 days have been compared.

Data on weight loss versus duration of exposure are shown in Fig. II.B.1. Carbon contents before and after test are listed in Table II.B.1. During the first nine months, the low-carbon grades lost more weight than did the regular stainless steels. The rate of weight loss decreased most

Fig. II.B.1. Corrosion (Weight Loss) of Types 304, 304L, 316, and 316L Stainless Steel Exposed to Sodium at 650°C (Cold Trap at 115°C)

strikingly for Type 304 stainless steel. This steel also displayed the lowest corrosion rate and the lowest weight loss for the total exposure. The Type 304L stainless steel lost the greatest amount of the carbon during the total exposure (see Table II.B.1); in fact, the carbon loss represented about 70% of its total weight loss. For the other three alloys, the material lost was comprised largely of the metallic constituents. Microprobe examination of selected cross-sectional areas indicated a slight depletion of chromium on the surface. Examination for carbon and nickel has not been completed.

TABLE II.B.1. Carbon Analysis of the Steels Subjected to Long-term Corrosion Testing

Types of Stainless Steel	Carbon Content (w/o)		Carbon Lost	
	Before Test	After 360 days Test	(%)	(μg/cm ²)
304	0.057	0.037	35.0	19
304L	0.031	0.026	16.0	4
316	0.063	0.057	9.5	6
316L	0.023	0.021	8.7	2

Metallographic examination of locally corroded regions revealed intergranular penetration in all four alloys. With the exception of Type 304 stainless steel, the depth of penetration increased with increasing exposure time. For Type 304 stainless steel, no penetration was observed after three months of exposure; after six months, typical penetrations ranged from 3 to 9 μ. No further change occurred over the next six months of additional exposure. At the time of final examination, maximum penetration depths for Types 304L, 316, and 316L stainless steel were 22, 12, and 30 μ, respectively.

Results of microhardness traverses of the sample cross section are given in Figs. II.B.2 and II.B.3. Microhardness values after exposures of 90 and 180 days are higher than those after 270 and 360 days, and also higher than those prior to testing. These results suggest hardening caused by precipitation of carbide during the first 90 days, followed by slow agglomeration and softening, similar to overaging. Additional information on the phases present in the alloys after exposure to sodium will be developed by chemical, metallographic, and X-ray analysis.

Fig. II.B.2

Microhardness Profiles of Types 304 and 304L Stainless Steel after Exposure to Sodium at 650°C. Exposure times: 90 days (◇), 180 days (○), 270 days (△), 360 days (●); unexposed samples (□).

Fig. II.B.3

Microhardness Profiles of Types 316 and 316L Stainless Steel after Exposure to Sodium at 650°C. Exposure times: 90 days (◇), 180 days (○), 270 days (△), 360 days (●); unexposed samples (□).

III. GENERAL REACTOR TECHNOLOGY

A. Applied and Reactor Physics Development

1. Theoretical Reactor Physics--Research and Development

a. Theoretical Reactor Physics

(i) Evaluation of Cross-section Data (D. A. Meneley)

Last Reported: ANL-7581, p. 81 (June 1969).

The original version of molybdenum cross sections prepared for ENDF/B gives too high a capture cross section, especially in the range from about 1 to 20 keV. A new version was prepared in which the capture cross section was revised. New resolved parameters were supplied for the energy range below 1 keV, although these do not lead to a capture cross section much different from the original one. Unresolved parameters along with a smooth background replace the original smooth capture cross section from 1 to 100 keV. These data were largely based on the parameters of Musgrove* and the recommended capture cross section of Poenitz and Kallfelz.** These unresolved parameters should yield a much more accurate capture cross section than in the original evaluation, as well as allowing self-shielding and Doppler calculations.

New ENDF/B compilations for the isotopes U-235, U-238, Pu-239, Pu-240, and Pu-241 are being prepared by members of the CSEWG. In this connection unresolved resonance parameters for Pu-241 and U-235 are being obtained by fitting average fission and capture cross sections using Fortran program UR. For Pu-241, Petrel fission data are being fit, and the capture cross section is being calculated with some guidance from measured total cross sections below 1 keV. Since there are almost no capture data available above the resolved resonance range, the capture cross section calculated from the parameters is quite uncertain. For U-235, the ORNL-RPI fission and capture data† are being fit over much of the unresolved range.

(ii) Reactor Computations and Code Development (B. J. Toppel)

Last Reported: ANL-7577, pp. 128-134 (April-May 1969).

(a) Fuel-cycle Package. By use of the ARC fuel-cycle package the change in k_{eff} over the operating cycle was underestimated in the preliminary search procedure because of the low plutonium buildup

* Musgrove, A. R. de L., AAEC/E198 (May 1969).

** Poenitz, W., and Kallfelz, J., Reactor Physics Division, private communication.

† de Saussure, G., et al., Simultaneous Measurement of the Neutron Fission and Capture Cross Sections for ^{235}U for Incident Neutron Energies from 0.4 eV to 3 keV, ORNL-TM-1804 (Nov 1967).

calculated in the axial blankets at the beginning of cycle. This led to a low enrichment guess from the preliminary search. To improve the calculation of the change in k_{eff} over the operating cycle, a one-burn-step subinterval is repeatedly used with one enrichment to obtain the cyclic mode* until the change in k_{eff} over the cycle converges. The most important effect observed has been a significant increase in the beginning of cycle k_{eff} .

The three levels of search procedures in the fuel-cycle package are as follows: In the preliminary search procedure, one burn-step subinterval is utilized in obtaining the cyclic mode with an enrichment and burn-step time specified as input. The above procedure is repeated until the change in k_{eff} over the cycle converges. At this point the burn-step time, which would give the desired burnup, is estimated. By use of this burn-step time and a second enrichment specified in the input, the cyclic mode is again obtained. A linear search of enrichment versus the multiplication constant is then initiated until an enrichment is obtained which gives the desired multiplication constant at the specified time in the cycle.

In the intermediate search procedure, the more general search procedures* are initiated with the exception that the iterations for the flux solution* at each time point in the cycle and the iterations for the cyclic mode are not done. By use of these procedures the burn-time satisfying the desired burnup and the enrichment giving the desired multiplication constant at the specified time in the cycle are obtained.

The final search procedure with iterations on the flux solution at each time point and iterations on the cyclic mode is then initiated.

2. Nuclear Data--Research and Development

a. Reactor Code Center (M. Butler)

Last Reported: ANL-7581, pp. 88-89 (June 1969).

During July and August, twelve program packages were added to the Center library; five were replacements of earlier library versions containing new features, improvements, or corrections.

Of the four new programs incorporated, two were supplied by the Knolls Atomic Power Laboratory and two by Gulf General Atomic. The KAPL programs are ACC No. R378 TUBE for the tube-stress analysis of U-tube-type heat exchangers, and ACC No. R382 RAPP for computing flow resistance and pressure for high-velocity flow of steam-water mixtures. These are both CDC-6600 versions. The Gulf General Atomic programs are ACC No. 379, SAFE-2D for elastic stress analysis of plane and axisymmetric

*Reactor Physics Division Annual Report, ANL-7310 (Jan 1968), pp. 493-501.

composite structures, and ACC No. 380, GATT, a 3-dimensional few-group neutron-diffusion-theory program for use with a hexagonal core configuration geometry. The GGA programs are operable on the UNIVAC 1108.

Two new machine versions of existing library programs were received during this report period. These were an IBM-360 version of the VARI-QUIR program (ACC No. 212) prepared by the University of Missouri, and an IBM-7094 version of the GAROL program (ACC No. 219) submitted by the NASA Lewis Research Center.

Corrections have been received from the originating installation, Westinghouse Atomic Power Division, and incorporated in the LEOPARD depletion program for the IBM-360 (ACC No. 279).

The five replacements made were:

1) ACC No. R80 SOR II; a new CDC-6600 version of this stress-analysis code was supplied by the originating installation, KAPL, to provide the punched-card output required by the auxiliary SORSDB program.

2) ACC No. R282 SEAL-SHELL-2; a new CDC-6600 version of this program to allow the reference surface of the shell to be placed anywhere between the inside and outside surfaces was received from the BAPL authors.

3) ACC No. 298 GGC4; a new UNIVAC 1108 version of this GGA multigroup cross-section code was submitted.

4) ACC No. 354 CINCAS; a corrected version of this IBM-360 program was received.

5) ACC No. 212 VARI-QUIR; a Fortran IV version of this program for the CDC-6600 replaced the original Westinghouse Astronuclear Laboratory's IBM-7094 package.

B. Reactor Fuels and Materials Development

1. Fuels and Claddings--Research and Development

a. Behavior of Reactor Materials

(i) Experimental Studies of Swelling Mechanisms and Gas Release in Fuel Materials

(a) Interactions between Gas Bubbles and Moving Grain Boundaries (S. R. Pati and P. S. Maiya)

Last Reported: ANL-7577, p. 142 (April-May 1969).

In order to study dragging of helium bubbles by migrating grain boundaries, several single crystals of copper were bombarded with 46-MeV alpha particles. Each specimen (1/4 by 1/4 by 1/4 in.) was irradiated to a total dose of 7 μ A-hr in a 5/16-in.-dia beam. A uniform concentration of helium to a depth of 0.009 in. was obtained by use of a rotating aluminum disk (varying in thickness from 0.006 to 0.032 in.) in front of the specimen during the alpha bombardment. Specimen temperature was maintained below 150°C by water cooling the aluminum specimen holder. Irradiation to a dose of 7 μ A-hr yielded 0.7×10^{-4} atom fraction of helium in the bombarded zone.

To form helium bubbles large enough to be visible under an optical microscope, the specimen was given two successive anneals, one at 816°C for 48 hr, and the other at 1020°C for 8 hr. The irradiated face of the specimen was then electroplated with copper to preserve the edges, as well as to support the hardness-indentation load. Hardness indentations were placed in the center of the narrow bubble band on a face perpendicular to the irradiated surface by use of a Brinell ball of 1-mm diameter with a load of 20 kg. The specimen was then annealed in vacuum ($<10^{-5}$ Torr) to allow recrystallization, sectioned through the center of the indentation by spark machining, mounted, and polished. Each specimen was mechanically polished on 4/0 emery paper, and then electropolished for about 5-10 min in a solution of 1/3 HNO₃ and 2/3 CH₃OH, cooled to -25°C in a bath of dry ice and acetone. Careful mechanical and electrolytic polishing was required to reveal optically the details at the recrystallization front.

During the annealing, new grains nucleated in the plastically deformed region close to the indentation and grew outwards into the deformed crystal. Close to the indentation, where the driving force for migration of the boundary was large, no obvious change in the distribution of bubbles occurred. Further from the indentation, where the driving force was smaller, the grain boundaries that formed the front between the deformed and the recrystallized material had started to drag the bubbles.

Figure III.B.1(a) shows a denuded region, where bubbles have been swept out of the matrix, and also the accumulation of bubbles on the moving grain boundary. Once the boundary is pinned by the bubbles, its further outward movement is controlled by the pinning force that the bubbles exert. During subsequent annealing of the specimen, the grain boundaries drag the bubbles along, leaving a bubble-free band on the trailing side of the moving boundaries.

Fig. III.B.1. Section through a Copper Specimen Containing Helium Bubbles after Annealing to Cause Sweeping of the Grain Boundary. Note the bubble-free zone adjacent to the moving grain boundary. Magnification 500X. Dark field illumination.

In order to study bubble sweeping as a function of time at constant annealing temperature, the same specimen was isothermally annealed for various times, repolished, and photographed. The successive measurements of band width were made on the same boundary to reduce scatter. The geometrical configuration of the recrystallization front did not change significantly during annealing cycles, so that measurements of the band width could be made and compared for corresponding points on the same front. Figure III.B.1(b) shows the swept region after reannealing at 990°C for 6 hr. Comparison of Figs. III.B.1(a) and III.B.1(b) shows the enlargement of the bubble-free region with greater annealing time at constant temperature. The time dependence of the width of the bubble-free zone was studied at 990°C, and a preliminary analysis of the data indicates that the width increases parabolically with annealing time. This behavior is similar to the dragging of oxide inclusions in a metal matrix by moving grain boundaries.*

The kinetics of the sweeping of inert gas bubbles are being studied in a number of specimens irradiated under identical conditions. The time dependence of the width of the bubble-free zone at several temperatures will furnish information on the activation energies associated with the dragging process, and enable the sweeping mechanisms to be determined. Bubble size will also be varied by use of different annealing treatments, as well as by variation of the irradiation dose.

*Ashby, M. F., and Centamore, R. M. A., The Dragging of Small Oxide Particles by Migrating Grain Boundaries in Copper, *Acta Met.* **16**, 1081 (1968).

(ii) Solid-fission-product Swelling (A. E. Dwight)

Last Reported: ANL-7577, pp. 143-144 (April-May 1969).

The white metallic inclusions formed in $\text{UO}_2\text{-PuO}_2$ irradiated in a fast-neutron flux have a hexagonal crystal structure and are based on the epsilon phase of the Mo-Rh binary system. Further work has shown that the epsilon phase in the ternary Mo-Ru-Rh system occupies a broad single-phase field, and that solid solubility of technetium and palladium in the epsilon phase is possible.

Two series of Mo-Ru-Rh alloys, one containing 20 a/o Ru and the other 40 a/o Ru, were prepared by arc-melting. The alloys were annealed at 1140°C ; crushed powder and filings from the alloys were annealed at 900°C . Unit-cell constants of the hexagonal epsilon phase were measured, and the volume of the unit cell was calculated. Figure III.B.2 shows the values of a_0 , c_0 , and V/M for these alloys. The epsilon phase is stable in a single-phase region that extends for at least 30 a/o Rh, at both the 20- and 40-a/o Ru concentrations.

Fig. III.B.2

Lattice Parameters and Unit Cell Volume of Mo-Ru-Rh Alloys. (a) a_0 , Å; (b) c_0 , Å; and (c) unit cell volume, Å³. Single-phase alloy is designated by O, and the 2- or 3-phase alloy is designated by ●.

An alloy with the same composition as the fission-product ingot formed in the $\text{UO}_2\text{-20 w/o PuO}_2^*$ was prepared by arc-melting the elemental constituents on a water-cooled copper hearth in an inert atmosphere. The composition of the prepared alloy is given in Table III.B.1. The charge weighed 2.3184 g, and the button weighed 2.3048 g, with a melting loss of 0.59%.

The button was annealed for two days at 1130°C in an evacuated capsule and then air cooled. Powder was made by crushing, and Debye-Scherrer patterns were taken with copper X radiation. The lines

*O'Boyle, D. R., and Brown, F. L., Observations on Metallic Ingots Formed during Irradiation of Mixed-oxide Fuel, Trans. Am. Nucl. Soc. 11(1), 101-102 (June 1968).

were not sharp, probably because of the cold work produced in making the powder. All lines were indexed and were found to belong to a hexagonal close-packed structure, with $a_0 = 2.736 \text{ \AA}$, $c_0 = 4.439 \text{ \AA}$, $c/a = 1.59$, and volume of the unit cell equal to $28.19 \text{ \AA}^3$. The volume of the unit cell is approximately the same as that of a ternary 29 a/o Mo-42 a/o Ru-29 a/o Rh alloy. The absence of any lines due to a second phase indicates that the technetium and palladium substitute for molybdenum, ruthenium, or rhodium atoms in the hexagonal lattice.

TABLE III.B.1. Composition of Simulated Fission-product Alloy

Element	Nominal Composition (a/o)	Calculated Composition (w/o)
Mo	20	19.17
Tc	17	16.82
Ru	48	48.49
Rh	13	13.36
Pd	2	2.16

(iii) Migration of Major Fuel Constituents (R. Natesh and D. R. O'Boyle)

Last Reported: ANL-7577, p. 3 (April-May 1969).

The radial redistribution of plutonium and uranium in a specimen from fuel element HOV-15 was studied by use of a shielded electron microprobe. The fuel element contained UO_2 -20 w/o PuO_2 (fully enriched uranium) and had an initial smear density of 79.8% of theoretical. The fuel element was irradiated in EBR-II to 3.5 a/o burnup at a maximum linear power rating of 21.4 kW/ft, with about 23 vol % of the fuel molten during irradiation. The specimen being examined was a cross section located about 1/4 in. from the bottom of the element.

A shielded microprobe was used to measure uranium and plutonium concentrations simultaneously. Measurements were made every 3 mils along a radius from the central void to the fuel-cladding interface. A computer program, Microprobe Analysis General for Radioactive Materials (MAGRAM), was used to correct the X-ray intensity data from the microprobe. MAGRAM, which is a modified version of the MAGIC II program,* was written specifically for the analyses of radioactive samples. The program corrects X-ray intensity data obtained with the microprobe for the following effects: (i) background due to the continuous spectrum,

*Gray, L. J., Doctoral Dissertation, University of Illinois, Urbana, Illinois, 1969.

(ii) background due both to scattered secondary and to fluorescent radiation, (iii) beam-current drift, (iv) detector dead-time losses, (v) absorption effects, (vi) characteristic line fluorescence, and (vii) atomic-number effects. The corrected data are then listed in tabular form and graphed as CALCOMP plots.

Figure III.B.3(b) shows the distribution of plutonium along a radius of the specimen. The arrows in the centers of Figs. III.B.3(a) and

Fig. III.B.3. Distribution of Plutonium plus Uranium (a) and Plutonium (b) in Fuel Element HOV-15 Irradiated to 3.5-a/o Burnup, Molten Center

III.B.3(b) indicate the location of the melt boundary as determined optically. In agreement with previous results (see also Progress Reports for February 1968, ANL-7427, pp. 102-104; and September 1967, ANL-7382, pp. 76-77), the plutonium concentration increased and the uranium concentration decreased at higher irradiation temperatures in the solid region of the fuel. The plutonium concentration near the central void, measured in fuel that was molten during irradiation, increased from a nominal composition of 17.7 w/o before irradiation to about 35 w/o after irradiation--an increase of about a factor of two.

Figure III.B.3(a) shows the change in the total concentration of plutonium and uranium along the same radius shown in Fig. III.B.3(b). The total content of plutonium plus uranium decreased in the molten fuel region as the temperature increased. This observation

suggests that oxygen might have migrated toward regions of higher temperature in the fuel element during irradiation.

b. Chemistry of Irradiated Fuel Materials (C. E. Crouthamel)

(i) Postirradiation Studies of Reactor Fuel and Cladding

Last Reported: ANL-7577, pp. 144-149 (April-May 1969).

Cross sections of two irradiated UC-20 wt % PuC fuel pins have been examined with an electron microprobe. One of the fuel pins (SMV-1)

was clad with Type 316 stainless steel and had been irradiated in EBR-II to 2.6-at. % burnup; the second pin (SMV-2) was clad with Type 304 stainless steel, and had been irradiated in EBR-II to 6.9-at. % burnup. The areas of principal interest in the microprobe study were the fuel-cladding interfaces.

Electron-microprobe examination showed an interaction zone at the fuel-cladding interface of each pin. The result of this interaction was the formation of separated bands of the stainless steel components. Small amounts of nickel migrated out of the cladding and penetrated the fuel slightly. A chromium-rich band of porous cladding formed between the nickel zone and the cladding material. The depths of attack of the cladding material were estimated to be about $7\text{ }\mu\text{m}$ for the fuel with the lower burnup and about $15\text{ }\mu\text{m}$ for the fuel with the higher burnup. The cladding-interface region was free of cesium and iodine fission products. Cesium was detected at relatively low concentrations in the peripheral areas of the fuel matrix, but did not appear to have moved into the nickel-rich band or into the cladding-interaction zone.

The extent of transport of nickel in the carbide fuels was small compared with that of iron and chromium in stainless steel-clad oxide fuels (see ANL-7577). The migration of nickel could be accounted for by a carbonyl transport process, similar to the Mond process for producing nickel metal. In the carbide fuel, the transport process would be the reaction of nickel in the cladding with carbon monoxide to form nickel carbonyl, followed by the vaporization and migration of the nickel carbonyl to hotter areas of the fuel, where it subsequently decomposes.

c. Thermodynamics of Fuel Materials

(i) Total Vapor Pressures and Carbon Potentials in the Ternary U-C-Pu System (P. E. Blackburn and M. Tetenbaum)

Last Reported: ANL-7577, pp. 149-151 (April-May 1969).

The study of the vaporization behavior of the uranium-carbon system is continuing. Measurements of the total pressure of uranium-bearing species and carbon activity are being made as a function of temperature and UC_x composition, using the transpiration method with hydrogen-methane mixtures as carrier gases. Emphasis has been placed on measuring carbon activities in the uranium-carbon system; these measurements will ultimately be extended to plutonium carbides.

Values for the enthalpy of vaporization of uranium monocarbide were calculated, assuming monatomic carbon as the principal gaseous species, from the reaction

and the relationship

$$\Delta H_{298}^{\circ} = -RT \ln K - T \Delta \left(\frac{G_T^{\circ} - H_{298}^{\circ}}{T} \right),$$

where the equilibrium constant K is $p_U p_C$ and $\Delta[(G_T^{\circ} - H_{298}^{\circ})/T]$ is the change in the free energy function. The partial pressure of $C_1(g)$ was estimated from our carbon activity measurements (see ANL-7577) and the pressure of C_1 in equilibrium with graphite.* Storms** adjusted vapor pressure measurements were used to estimate the total pressure of $U(g)$. Free energy function values were obtained from Schick for $C_1(g)$ and $U(g)$, and from Storms for $UC_{1.00}(s)$. The results of these calculations, for the temperatures of our carbon activity measurements, are as follows:

Temperature (°K)	ΔH_{298}° (kcal/mol)
2155	322.4
2255	322.5
2355	320.0
2455	321.9
Avg.	322.2 ± 1.2

For comparison, the enthalpy of vaporization was also derived from the following thermodynamic cycle for $UC_{1.00}$:

Reaction	ΔH_{298}° (kcal/mol)
$UC(s) = U(s) + C(s)$	23.2 ± 1
$U(s) = U(g)$	126.3 ± 1
$C(s) = C_1(g)$	170.9 ± 0.5
$UC(s) = U(g) + C_1(g)$	320.4 ± 1.5

The value of $\Delta H_{298}^{\circ} = 23.2$ kcal/mol for the initial reaction in the cycle is based on the combustion measurements of Storms and Huber,[†] who obtained values of -23.2 ± 0.9 and -23.0 ± 1.0 kcal/mol for the heats of formation of $UC_{0.996}$ and $UC_{1.032}$, respectively. For the heat of sublimation of uranium, we used the recent value obtained by Ackermann and Rauh^{††} from mass-spectrometric and effusion measurements. The good agreement of the two values for the enthalpy of vaporization of $UC_{1.00}$ is encouraging.

* Schick, H. L., Thermodynamics of Certain Refractory Compounds, Vol. II, Academic Press, New York (1966).

** Storms, E. K., The Refractory Carbides, Academic Press, New York (1967), Chap. XI, pp. 205-213.

† Storms, E. K., and Huber, E. J., J. Nucl. Mater. **23**, 19 (1967).

†† Ackermann, R. J., and Rauh, E. G., J. Phys. Chem. **73**, 769 (1969).

d. Metallic Fuels

(i) Fuel-element Performance (H. V. Rhude and R. Natesh)

Last Reported: ANL-7595, pp. 96-97 (July 1969).

Microprobe analysis has been completed of a transverse section taken from the midlength of fuel element ND24, which was irradiated in EBR-II to an estimated burnup of 6.9 a/o. Although the original U-15 w/o Pu-10 w/o Zr fuel appeared to have restructured into three different zones in the metallographic studies, the microprobe analysis indicated that there were essentially four zones, with the outer zone being subdivided into two different compositional zones. Sample-current photographs of the specimen taken with the microprobe reveal that each zone is composed of two major phases in varying mixtures; these phases appear as a dark phase and a light phase. Quantitative microprobe analyses of typical phase structures in each zone are given in Table III.B.2 for U, Pu, and Zr. The phases have not yet been identified. Sodium also was detected in the porous central and outer regions, with local concentrations as high as from 1 to 6 w/o. A full transverse section of fuel from the same region as the microprobe specimen was analyzed for sodium by emission spectroscopy and was found to contain 0.05 w/o sodium (approximately 0.5 a/o).

TABLE III.B.2. Quantitative Analysis of Restructured Fuel Zones in U-15 w/o Pu-10 w/o Zr Alloy Irradiated to an Estimated Burnup of 6.9 a/o

Element	Composition (w/o)							
	Central Zone		Intermediate Zone		Mid-outer Zone		Far-outer Zone (Near cladding)	
	Dark Phase	Light Phase	Dark Phase	Light Phase	Dark Phase	Light Phase	Dark Phase	Light Phase
U	80	50	88	73	85	65	87	65
Pu	7	25	8	20	10-15	15	5	12
Zr	10	25	3	7	1-5	12	10	25

2. Radiation Damage on Structural Materials--Research and Development

a. In-Reactor Creep Studies

(i) Determination of Void Size (S. D. Harkness)

Last Reported: ANL-7595, pp. 97-100 (July 1969).

Void sizes have been measured in four samples of Type 304 stainless steel. The results, presented in Table III.B.3, show that irradiations at lower temperatures produce higher number densities of smaller voids than similar irradiations at higher temperatures. The size distribution of voids formed at lower temperatures is also narrower than that for the higher temperatures.

TABLE III.B.3. Void Sizes in Irradiated Type 304 Stainless Steel

Sample	Irradiation Temperature (°C)	Fluence (10 ²² n/cm ²)	Number of Voids Measured	Average Void Diameter ^a (Å)	Maximum Void Diameter (Å)	Standard Deviation (Å)	Void Number Density (10 ¹⁵ /cm ³)
Safety-rod	426	5.0	160	200	412	49	5.9 ^b
Guide Thimble 3-C-2	413	8.2	160	164	280	43	17.8 ^b
XG05 Capsule	510	4.8	150	277	680	133	0.49 ^c
XG05 Cladding	610	4.8	175	500	1400	275	0.06 ^c

^a±10%.^bCalculated from immersion density and void diameter.^cTEM measurement, ±50%.

3. Techniques of Fabrication and Testing--Research and Development

a. Nondestructive Testing Research and Development

(i) Development of Electromagnetic Testing Techniques (C. J. Renken)

Last Reported: ANL-7577, pp. 158-160 (April-May 1969).

Multiperture transducers with apertures of 1.25 mm have been constructed and their performance evaluated. The response of the new transducers to point defects is almost identical to that of the older multiperture transducers, which had apertures of 1.77 mm. Therefore, the smaller aperture size does not improve the resolution for the detection of internal defects in tubing. The smaller apertures do have a geometrical advantage, however, in that more of them can be placed around the circumference of a tube in a single plane without development of cross coupling. For example, six apertures normal to the radii of the tube can be located in one plane for tubing as small as 5.5 mm in outside diameter. With the older design, two separate banks of three apertures each were needed to completely cover the smaller tubing sizes. The placement of the six apertures in one plane provides more uniform sensitivity and better noise suppression.

A jacket-tubing test system with six apertures has been installed at South Dakota School of Mines and Technology for use in a signal-processing study. One of the most interesting parts of this study involves pattern recognition. The variety of the patterns that can be recognized depends partly on the dimensionality of the signal source. The six-aperture equipment provides a multidimensional set of signals that should make possible the recognition of a large variety of abnormalities in jacket tubing.

4. Engineering Properties of Reactor Materials--Research and Development

a. High Temperature Mechanical Properties of Ceramic Fuels

(i) Adiabatic Elastic Constants of Monocrystalline UC (J. L. Routbort and P. S. Maiya)

Not previously reported.

Measurements of the adiabatic elastic constants of UC at high temperature should yield useful information on the bonding and the structure of this compound. The measurements would also be interesting because at 300°K the elastic constant C_{44} has a positive temperature coefficient,* which is very unusual for this class of materials. Furthermore, if order-disorder transformations occur in UC, as they do in some of the refractory carbides, they would be detected in the temperature dependence of the elastic constants. Finally, one of the least investigated and least understood areas is the relationship between the elastic and the plastic properties in the monocarbide compounds. Some exploratory measurements of the room-temperature elastic constants of single crystals of UC have been made; attempts have also been made to extend the measurements to higher temperatures.

The hyperstoichiometric UC (4.96 wt % C) used in this study was grown by electron-beam zone melting at Atomics International, and provided to ANL by Idaho Nuclear Corp. The Laue pattern obtained by back reflection of X rays revealed the presence of subgrains with orientation differences of approximately 3°. Annealing in helium for 40 hr at 2000°C did not improve the degree of perfection. Specimens 3-6 mm thick were cut from a long crystal by spark machining, oriented, and hand lapped on diamond paste to a 1- μ finish by a technique developed by Fisher.** Three oriented crystals, one with opposite faces parallel to (100) (approximately 4 mm thick), and the other two with faces parallel to (110) (approximately 1 and 4 mm thick, respectively) were prepared. The surfaces were flat and parallel to within 0.0002 in. The shear and longitudinal velocities were measured at room temperature by the phase-comparison technique** from 15 to 70 MHz. The best results were obtained with the use of "Nonoq" to bond the sample to the buffer rod for longitudinal waves, and with Dow Corning resin 276-V9 for the shear modes.

The results for the velocities are compared with previously published data in Table III.B.4. The errors indicated in the table have been estimated from the uncertainties in the frequency determinations and in the

*Graham, L. T., and Chang, R., Compounds of Interest in Nuclear Reactor Technology, Waber, J., et al., eds. AIME, New York (1964), p. 409.

**Fisher, E. S., and McSkimin, H. J., J. Appl. Phys. 29, 1473 (1958).

thickness measurements. The phase correction was experimentally determined to be negligible. Other sources of errors, such as those resulting from orientation, from extrapolation of data to a limiting velocity, from nonparallelism of faces, and from temperature, have not been included.

TABLE III.B.4. Room-temperature Velocities and Elastic Constants of Uranium Carbide

Material	Velocity x 10 ⁻⁵ (cm/sec)					Elastic Constants x 10 ⁻¹² (dyne/cm ²)		
	(100) Longitudinal	(100) Shear	(110), Polarized [110]	(110), Polarized [100]	(110) Longitudinal	C ₁₁	C ₁₂	C ₄₄
This Work 4.96 wt % C	-	-	-	2.173	4.450	-	-	0.642
	4.852 ±0.004	2.220 ±0.004	2.972 ±0.002	-	4.430 ±0.002	3.204	0.797	0.671
Graham and Chang ^a	4.837	2.1947	-	-	4.432	3.184	0.862	0.6555
Graham et al. ^b	-	-	-	-	-	3.20	0.84	0.646

^aGraham, L. T., and Chang, R., *Compounds of Interest in Nuclear Reactor Technology*, Waber, J., et al., eds. AIME, New York (1964), p. 409.

^bGraham, L. T., Nadler, H., and Chang, R., *J. Appl. Phys.* **34**, 1572 (1962).

The results for the thin crystal do not completely determine the elastic constants. The results are also more unreliable because of the large geometrical dispersion exhibited in the curves of velocity versus frequency. The computed values for the elastic constants obtained from these velocities by the usual formulas and a density of 13.61 g/cm³ are also tabulated in Table III.B.4.

Since four independent determinations of the velocities were made on the thick crystals, the internal consistency of the results may be checked as follows:

$$\sqrt{\frac{C_{11} - C_{12}}{2\rho}} = 2.9737 \times 10^5 \text{ cm/sec.}$$

This value is within 0.06% of the measured value of shear velocity for (110) polarized in the [110] direction. The disagreement with the published data may be attributed to the difference in stoichiometries, which would affect the amount and the distribution of the second phase, and may have a pronounced effect on the elastic constants. Before the implications of these results may be discussed, a systematic investigation of UC single crystals of various stoichiometries must be completed. This work is planned.

Two difficulties were encountered in attempting to extend these measurements to 1000°C. Bonding of the specimen to the buffer rod at high temperatures was only successful in a few cases, and when it was, the sound was so highly attenuated that reliable measurements of the velocity

could not be made. Both "flubber" (a rubber-like phenotic resin*) and "VHT" coating (Sperex Corp.) were used. The major problem is that the coating does not uniformly adhere to the surface after curing. This failure is probably caused by surface imperfections (second phase "pullout," cracks, etc.).

The high attenuation is probably caused by a high dislocation density and by internal cracks, which are sources of large scattering. In two cases the crystals cracked after repeated bonding and handling, which provides evidence for the existence of internal cracks. The fact that the subgrains did not disappear after a high-temperature anneal indicates that a large number of dislocations had already been locked into a polygonized structure. The high densities of dislocations and cracks may be overcome in our future work by use of slower zoning speeds in order to prepare more perfect crystals. The presence of second phase may be avoided by using stoichiometric crystals.

Defects in the single crystals prevented the extension of these measurements to higher temperatures. Our future work will include these measurements with crystals of UC of better quality as well as of other refractory carbides, and a careful study of the relationship between elastic and plastic properties will be made.

*LT-424F Primer manufactured by the Bloomingdale Rubber Co.

C. Engineering Development--Research and Development

1. Development of Master-Slave Manipulator Systems (R. C. Goertz)

Last Reported: ANL-7581, p. 97 (June 1969).

a. Modification of Mark-E4A Electric Master-Slave Manipulator

When the budget for the development of manipulator systems was cancelled, all work was brought to a stop. Partially fabricated components for the slave arm were set aside; the slave arm was reassembled with the old components so it can be demonstrated.

b. Development of High-performance DC Servomotor and Servo Drive Unit

Fabrication work was stopped on the high-performance moving-coil servomotor that was being developed for a master-slave manipulator that would have a load capacity of 75-100 lb. The motor was designed to have a merit factor T^2/Jw of greater than 2000/sec, where T is torque in Newton-meters, J is inertia in kg-meters squared, and w is armature I^2R power in watts.

2. Heat Transfer and Fluid Flow

a. LMFBR Burnout Limitations (R. J. Schiltz and R. Rohde)

Last Reported: ANL-7581, p. 102 (June 1969).

(i) Preparation of Apparatus. Loop construction is proceeding. More stringent and additional safety and quality-assurance requirements have been adopted, necessitating changes in components or more detailed examination of components. For instance, the method of attaching the 1.5-in. valves was changed from a socket-welded connection to a butt weld; when 11 available valves were disassembled and radiographed, six were found to be acceptable. Transition pieces are being fabricated for the six valves needed for the loop.

The duct system for the air-cooled heat exchanger will be rerouted to meet additional safety requirements designed to prevent the release of sodium oxide to the environs in the event of a sodium leak in the heat exchanger. The air duct also is being redesigned to have a double wall by addition of a stainless steel liner.

The piping system has been simplified because of the successful development of the electromagnetic helical induction pump. Thermal

stress considerations led to a design change in the connection of the bypass line to the plenum so that the line will enter the top flange.

The vacuum chamber was received and found to be acceptable. It has been positioned in the loop structure and the plenum has been installed atop the vacuum chamber. The superstructure for the loop is being extended to provide additional space for equipment for the tests.

b. Nonboiling Transient Heat Transfer (R. P. Stein)

Last Reported: ANL-7445, p. 112 (April 1968).

(i) Analyses of Heat-flux Transients. Engineering relationships to account for forced-convection heat transfer in ducts during wall-heat-flux transients were described previously (see Progress Report for March 1968, ANL-7438, pp. 102-105). Since then the relationships have been generalized further and refined. Because of interest in their application, the relationships are summarized here, and a table of coefficients is given for use in a special case.

In their present form, the relationships apply to a generalized annular space. They can be used to approximate a pin-bundle geometry by considering each pin to be surrounded by an equivalent annular space with turbulent velocities and eddy diffusivities corresponding to a zero-shear condition at the equivalent outer wall. The relationships for the generalized annular space are

$$t_{s,i} - t_B = \frac{q_i - q_j}{h_i(0)} + \frac{q_j}{h_i(1)} + \frac{D}{2k} \sum_{k=1}^{\infty} \frac{D^k}{D\theta^k} [R_{i,k}q_i + S_{i,k}q_j], \quad (1)$$

where

$$\frac{D^k q}{D\theta^k} = \left(\frac{\partial}{\partial z} + \frac{\partial}{\partial \theta} \right)^k q$$

$$= \frac{\partial q}{\partial z} + \frac{\partial q}{\partial \theta} \quad \text{for } k = 1$$

$$= \frac{\partial^2 q}{\partial z^2} + 2 \frac{\partial^2 q}{\partial z \partial \theta} + \frac{\partial^2 q}{\partial \theta^2} \quad \text{for } k = 2, \text{ etc.,}$$

and $R_{i,k}$, $S_{i,k}$, and β are dimensionless coefficients that are functions of Reynolds and Prandtl numbers and of annulus radius ratio (but are independent of θ and z), $t_{s,i}$ = surface temperature of wall "i," t_B = fluid bulk temperature, q_i = heat-flux density from wall "i," q_j = heat-flux density from

opposite wall, $h_i(0)$ = fully developed heat-transfer coefficient for case of q_i uniform and constant and $q_j = 0$, $h_i(1)$ = fully developed heat-transfer coefficient for case q_i uniform and constant and $q_j = q_i$, z = dimensionless axial distance = $\beta(\ell/D)$, ℓ = axial distance, D = hydraulic equivalent diameter, θ = dimensionless time = $\beta(\bar{u}\tau/D)$, $\bar{u}$ = average fluid velocity, τ = time, and k = fluid thermal conductivity.

Equation (1) is not strictly valid for very small values of time and of axial distance. Specifically, when $\theta < z$ it is required that $\bar{u}\tau/D \gg 1$, and when $\theta > z$, it is required that $\ell/D \gg 1$. Inaccuracies introduced by ignoring these requirements are comparable to those resulting from the use of fully developed heat-transfer coefficients in steady-state thermal entrance regions, and in practical calculations are not too serious.

The coefficients β , $R_{i,k}$, and $S_{i,k}$ are related to the eigenfunctions and eigenvalues of the following Sturm-Liouville problem:

$$LE_n(x) + \lambda_n g(x) E_n(x) = 0; \quad (2)$$

$$0 \leq x \leq 1;$$

$$E_n(0) = E_n(1) = 0,$$

where primes denote differentiation with respect to x ,

$$LE_n(x) = \frac{\{[1 + \text{Pr}\epsilon(x)/\nu] [R + (1 - R)x] E_n'(x)\}'}{R + (1 - R)x},$$

R is annulus radius ratio (inner radius divided by outer radius), x is x'/a , x' is radial distance measured from inner wall of annulus, a is annulus width, ϵ is eddy diffusivity for heat transfer, ν is kinematic viscosity, Pr is Prandtl number, $g(x)$ is $u(x)/\bar{u}$, $u(x)$ is local fluid velocity, and $\bar{u}$ is average fluid velocity.

Normalized eigenfunctions $\phi_n(x)$ are defined by

$$\phi_n(x) = E_n(x)/N_n, \quad (3)$$

where

$$N_n^2 = \frac{2}{1 + R} \int_0^1 [R + (1 - R)x] g(x) E_n^2(x) dx.$$

The coefficient β is given by

$$\beta = 4\lambda_1/\text{Pe}, \quad (4)$$

where λ_1 is the least nonzero eigenvalue, and Pe is the Peclet number, $D\bar{u}/\alpha$, with α the fluid thermal diffusivity.

If the subscript $i = 1$ represents the inner wall of the annulus and $i = 2$ the outer wall, then

$$R_{1,k} = (-1)^k \frac{2R\lambda_1^k}{1+R} \sum_{n=1}^{\infty} \phi_n^2(0)/\lambda_n^{(k+1)}; \quad (5)$$

$$S_{1,k} = (-1)^k \frac{2\lambda_1^k}{1+R} \sum_{n=1}^{\infty} \phi_n(0)\phi_n(1)/\lambda_n^{(k+1)}; \quad (6)$$

$$R_{2,k} = (-1)^k \frac{2\lambda_1^k}{1+R} \sum_{n=1}^{\infty} \phi_n^2(1)/\lambda_n^{(k+1)}; \quad (7)$$

$$S_{2,k} = RS_{1,k}. \quad (8)$$

Values of β and the coefficients $R_{i,k}$ and $S_{i,k}$ for the "narrow" annulus or parallel-plane case (i.e., for $R = 1$) are given in Table III.C.1. Note that for this special case, because of the symmetry $R_{1,k} = R_{2,k}$ and $S_{1,k} = S_{2,k}$. The values given in Table III.C.1 are based on the use of von Kármán's universal velocity profile with eddy diffusivities for heat transfer equal to those for momentum transfer and uniform at their maximum values in the central region of the duct.

TABLE III.C.1. Values of Coefficients for Parallel-plane Duct^a

Re	Pr	β	$-R_1$	R_2	$-R_3$	S_1	$-S_2$	S_3
10^4	0.00316	1.483	0.196	0.183	0.180	0.168	0.176	0.178
	0.01	0.518	0.179	0.167	0.164	0.153	0.160	0.162
	0.0316	0.213	0.141	0.130	0.128	0.119	0.125	0.127
	1	0.0757	0.0163	0.0138	0.0133	0.0119	0.0128	0.0130
3.16×10^4	0.00316	0.492	0.187	0.174	0.171	0.160	0.167	0.170
	0.01	0.196	0.151	0.140	0.138	0.128	0.135	0.136
	0.0316	0.102	0.0950	0.0873	0.0857	0.0794	0.0835	0.0847
	1	0.0601	0.00603	0.00522	0.00508	0.00461	0.00490	0.00499
10^5	0.00316	0.185	0.159	0.147	0.145	0.135	0.142	0.143
	0.01	0.0931	0.103	0.0952	0.0953	0.0868	0.0911	0.0924
	0.0316	0.0639	0.0501	0.0455	0.0446	0.0411	0.0433	0.0440
	1	0.0507	0.00221	0.00194	0.00189	0.00172	0.00182	0.00186
3.16×10^5	0.00316	0.0865	0.111	0.102	0.100	0.0930	0.0976	0.0990
	0.01	0.0576	0.0552	0.0503	0.0492	0.0454	0.0478	0.0486
	0.0316	0.0484	0.0218	0.0196	0.0191	0.0175	0.0185	0.0189
	1	0.0443	0.000804	0.000705	0.000686	0.000623	0.000662	0.000675
10^6	0.00316	0.0527	0.0599	0.0546	0.0535	0.0494	0.0521	0.0529
	0.01	0.0436	0.0242	0.0217	0.0212	0.0194	0.0205	0.0209
	0.0316	0.0407	0.00850	0.00753	0.00734	0.00669	0.00710	0.00723
	1	0.0394	0.000287	0.000251	0.000244	0.000222	0.000236	0.000240

^aFor this case $R_{i,k} = R_{j,k} = R_k$, and $S_{j,k} = S_{i,k} = S_k$; note sign designation in table headings for coefficients.

For engineering relationships, the usual "one-dimensional" energy equation for an incompressible fluid flowing through an annular duct can be written as

$$c\rho S\left(\bar{u}\frac{\partial t_B}{\partial \ell} + \frac{\partial t_B}{\partial \tau}\right) = A_1q_1 + A_2q_2, \quad (9)$$

where c is specific heat of fluid, ρ is density of fluid, S is cross-sectional area of duct, and A_i is heat-transfer area per unit length. Equation (1) serves as a "coupling" or boundary condition between heat transport in the fluid as given by Eq. (9) and heat conduction in the duct walls or in a reactor fuel element.

A variety of exploratory computations with Eq. (1) has shown that (a) in all "realistic" cases, the infinite series can be truncated at $k = 2$; (b) in most cases, truncation at $k = 1$ gives sufficient accuracy; (c) truncation at $k = 1$ always gives an improvement in accuracy over simple use of the steady-state heat-transfer-coefficient relation. Based on these observations, Eq. (1) truncated at $k = 1$ (or $k = 2$ in "severe" cases) is suggested as an improved engineering relation accounting for forced-convection heat transfer during flux transients, i.e., as a "coupling" or boundary condition for use with Eq. (9). By "improved engineering relation" is meant a more accurate, but still convenient, alternative to the use of the simple steady-state heat-transfer-coefficient relation. Note that Eq. (1) also includes the case of steady-state, nonuniform heat fluxes.

A computer program* solves Eq. (2) numerically. The program, which handles boundary conditions other than the derivative being zero at both boundaries, will be used to compute values of the coefficients of Table III.C.1 for other geometries, and for other methods of calculating turbulent velocity profiles and eddy diffusivities.

c. Fog-Flow Heat Transfer and Fluid Flow (R. P. Stein)

Last Reported: ANL-7561, pp. 76-78 (March 1969).

(i) Summary of Experimental and Theoretical Investigations.

The experimental phase of the fog-flow program has ended, and a final report is being completed.

The objective of the experiment was to determine the validity of a turbulent diffusion model as applied to liquid-droplet transport in the central core region of fully developed pipe flow. As an outcome of the analysis of data from the experiment, turbulent "particle diffusivities" (see Progress Report for March 1968, ANL-7438, pp. 105-106) were obtained for

*Kaganove, J., SLOB5, Applied Mathematics Division, Argonne National Laboratory.

Fig. III.C.1. Summary of Data on Particle Diffusivity

a range of droplet terminal velocities and mean-flow Reynolds numbers. Figure III.C.1, which is a summary of the particle-diffusivity data, supports the intuitive notions that heavy particles (large terminal velocity) diffuse less readily than do light ones and that turbulent mixing increases with mean-flow Reynolds number.

With the diffusivity results of Fig. III.C.1, the diffusion equation was used to calculate droplet-concentration distributions downstream from a source of droplets. The diffusion model, with a turbulent diffusivity independent of radial and axial coordinates, fits the data generally within 20%. The experiment results indicate that the diffusion model, with constant diffusivity, provides a reasonable description of droplet transport in the central region of turbulent pipe flow, at least for the range of droplet terminal velocities and mean-flow Reynolds numbers considered in the experiment.

3. Engineering Mechanics

a. Advanced Thermoelasticity (R. A. Valentin)

Last Reported: ANL-7581, p. 103 (June 1969).

(i) Solution of End-effect Problems Involving Nonplane Stress Fields in Short Cylinders and Contact Stresses between Cladding and Fuel. The elastic analysis of the stresses and deformation of a traction-free, heat-generating, finite circular cylinder has been completed. Figure III.C.2 illustrates the deformed shapes of the outer surface of finite cylinders having length-to-diameter ratios h of 0.5, 1.0, and 2.0 for the case of uniform internal heat generation and purely radial heat flow. The dimensionless displacements $\hat{u}_r$ and $\hat{u}_z$ are related to the true displacements by $(u_r, u_z) = [a^3 \alpha Q (1 + \nu) / 4k(1 - \nu)] (\hat{u}_r, \hat{u}_z)$, where a is the cylinder radius, α is the coefficient of linear thermal expansion, Q is the volumetric heat-generation rate, k is the thermal conductivity of the material, and ν is Poisson's ratio.

Fig. III.C.2

Shape of Finite Elastic Cylinder Deformed by Subjection to a Radial Temperature Variation due to Uniform Internal Heat Generation--with Traction-free Surfaces

Figure III.C.3 illustrates the departure from plane strain of a typical stress component $\hat{\sigma}_{\theta\theta}$ (the circumferential stress) at the cylinder surface ($\rho = 1.0$) and centerline ($\rho = 0.0$) for various length-to-diameter ratios h . The dimensionless axial coordinate is $\xi = z/a$, Poisson's ratio is $\nu = 0.25$, and the true stress is related to the dimensionless values by $\sigma_{\theta\theta} = [a^2 \alpha E Q / 4k(1 - \nu)] \hat{\sigma}_{\theta\theta}$, where E is Young's modulus. The relationship of these results to axially nonuniform interface pressure at the cladding-fuel interface in pellet-type fuel pins and the possibility of cladding "ridging" due to such loading is being studied. The combination of a solution such as that just completed with the deformations produced by cladding contact stresses has been initiated.

Fig. III.C.3

Variation of Circumferential-stress Component in Finite-length Heat-generating Cylinders of Various Length-to-Diameter Ratios h

b. Structural Dynamics Studies--Structure-Fluid Dynamics
(M. W. Wambsganss, Jr.)

(i) Preparation of Two Structural-Dynamics Test Loops
(B. L. Boers and P. L. Zaleski)

Last Reported: ANL-7595, p. 107 (July 1969).

Labor estimates for construction of the large test loop have been negotiated and approved; construction is scheduled to begin in September.

To study flow noise generated by the pump and system of the small test loop, pressures were measured at several locations in the loop piping wall. Pressure-time histories corresponding to a range of mean axial flow velocities were recorded on magnetic tape; the data are being processed on a spectrum analyzer.

(ii) Damping (P. L. Zaleski and M. W. Wambsganss, Jr.)

Last Reported: ANL-7581, pp. 105-107 (June 1969).

In the continuing study of damping in a flowing fluid medium, the influence of fluid viscosity on effective modal damping factor is being investigated. Initial tests are being carried out in static water with the viscosity varied by varying the water temperature. Damping factors are measured using the log-decrement technique. Preliminary results indicate the effect might be negligible relative to other damping mechanisms.

(iii) Tube-stop Impact (S. S. Chen and B. L. Boers)

Last Reported: ANL-7561, pp. 79-81 (March 1969).

A topical report on the theoretical analysis of a tube impacting with a motion-limiting stop located at the midpoint is being prepared. The analysis permits computation of dynamic displacements, bending stresses, and impact forces.

An experiment has been designed to study tube-stop impact. The experiment will be used to verify the assumptions and computed results from the theoretical analysis. A vibration-test fixture has been built; it will accommodate tubes up to 48 in. long. Design is continuing on the details of the stops and measurement methods.

D. Chemistry and Chemical Separations

1. Fuel Cycle Technology--Research and Development

a. Fluoride Volatility Processes

(i) Purification Procedures and Fission Product Chemistry (M. J. Steindler)

Last Reported: ANL-7595, pp. 109-110 (July 1969).

(a) Fission Product Chemistry. Adequate containment of iodine is a serious problem in the development of fuel-reprocessing methods for high-burnup fuels because iodine appears in effluent process streams in

primarily four forms (I_2 , HOI , CH_3I , and particulate) that have different sorption characteristics. One proposed concept is to convert all iodine-containing species to IF_5 by reaction with F_2 , CoF_3 , or BrF_5 , and to fix IF_5 by hydrolysis to IO_3^- or by conversion to a nonvolatile species such as KIF_6 . Exploratory experiments were performed in which elemental iodine in a helium stream was passed through a bed of CoF_3 at $350^\circ C$. The stream was then passed through a bed of KF at $150^\circ C$. Quantitative results were not obtained, but qualitative results indicate that the proposed method may be applicable for separating iodine from process off-gas streams.

(ii) Engineering-scale Development for FBR Fuels
(N. M. Levitz)

Last Reported: ANL-7595, pp. 110-112 (July 1969).

(a) Dense-phase Transportation of Granular Solids. Dense-phase pneumatic transportation is being evaluated as a method of transporting active granular wastes, as well as inactive granular solids. The apparatus previously described (see ANL-7595) was used in exploratory studies to obtain design information on the effect of the discharge-orifice diameter on the transport rate of the solids. With air pressures in the hopper of 50.1, 49.7, and 46.2 psig, the steady-state transport rates for 48-100 mesh alumina at ~ 0.042 cfm air flow (at $70^\circ F$ and 1 atm) were 167, 238, and 329 g/min, respectively, for discharge-orifice diameters of $3/32$, $3/16$, and $3/8$ in.

b. Compact Pyrochemical Processes

(i) Demonstration of Head-end Process (P. A. Nelson)

Last Reported: ANL-7595, p. 113 (July 1969).

The plans for experiments to be performed in the Plutonium Salt Transport Experiment alpha gloveboxes are being revised to allow for a shift in emphasis to pyrochemical head-end operations for aqueous processes. The glovebox and associated equipment that were to be used for decladding, reduction, and uranium recovery in the salt-transport process (glovebox 3) should be suitable for the new experimental program without any major modifications (see Progress Report for September 1968, ANL-7500, pp. 115-116). Glovebox 3 will be completed during September, and, after shakedown tests of the equipment, decladding experiments should begin during the first half of October.

Glovebox 3 has been helium leak-checked, and the automatic pressure-control system for the glovebox atmosphere has been tested in preparation for converting the atmosphere from air to helium. The piping

manifold for three of the six furnaces in the box has been completed and leak-checked, and the manifold for the remaining three furnaces is being fabricated. Side panels for the area below the glovebox are nearly complete.

Two of the three Mo-30 wt % W transfer lines to be used in box 3 have been fabricated and bent to the design configuration, and machining operations on parts for the third line have been completed.

Electrical power for box 3 has been run from a 75-kVA transformer on the service floor to the main power panel for the glovebox. All power, control, and instrumentation wiring for the furnace and transfer-line control panels has been installed, and wiring to the pressure-control switches and solenoid valves for the box is complete. Power, control, and instrumentation wiring has been connected by feed-throughs into the box, and thermocouple leads are currently being connected. The pressure-control panel for the furnace is about 85% complete.

(ii) Extraction Process Engineering Studies (R. D. Pierce)

Last Reported: ANL-7595, pp. 113-115 (July 1969).

Pyrochemical reduction of oxide fuel is performed using a Cu-Mg-Ca reduction alloy and a CaCl_2 -20 mol % CaF_2 reduction salt. During the reduction, the CaO byproduct dissolves in the salt. Because it is desirable to minimize the quantity of reduction salt used, an experiment was performed to determine the effect of various loadings of CaO in the salt on the mixing power required for the reduction. Calcium oxide loadings up to 18.5 wt % were used, which is almost double the solubility of CaO in the salt at the reduction temperature of 725°C.

The experiments were conducted using a mixing dynamometer. Data were obtained at mixing speeds between 300 and 700 rpm in a baffled crucible with a two-bladed flat paddle. The results of the experiments showed that, over the range of CaO concentrations studied, no appreciable change in power is required to achieve adequate mixing. These results indicate that high loadings of CaO in the reduction salt will not interfere with the mechanics of the reduction step.

In other work, various materials of construction are being tested for application in pyrochemical processes. Because niobium has shown excellent corrosion resistance to the metal and salt solvents that would be used in the liquid metal-molten salt contactors proposed for pyrochemical processing (see ANL-7595 and below), further tests were made using specimens of niobium that had been welded together. Four welded specimens (3/8 in. high by $2\frac{1}{4}$ in. wide by 63 mils thick) were tested in the form of agitator blades in a Mg-44 at. % Cu/ MgCl_2 -30 mol % NaCl-20 mol % KCl-3 mol % MgF_2 system at 700°C. The blades were mounted so that one

was in the metal phase, one at the metal-salt interface, one in the salt phase, and one in the vapor phase above the salt. The agitator was operated at 150 rpm for 142 hr.

All blades were in excellent condition after the test. The weld zone was sound and had retained its ductility. The hardnesses of both the weld and parent material were reduced by annealing at the test temperature, and the corrosion rates of both the weld and parent metals exposed to the liquid phases were less than 1 mil/yr.

Similar tests with coupons of both welded and unwelded Type 405 stainless steel indicated that this material has satisfactory corrosion resistance to the salt phase, but considerably less resistance than niobium to the metal phase. Stainless steel samples (~250 mils thick) that were exposed to the metal phase for 1000 hr suffered a 10.6% weight loss.

A graphic summary of the relative corrosion resistance of various materials tested during the last year is presented in Fig. III.D.1. Although the corrosion rates (presented in mils/yr) are based on short-term tests, they are probably fairly reliable for materials with relatively low corrosion rates (< 50 mils/yr). Tungsten, for which data are not included in the figure, possesses superior resistance to all metals and salts of process interest, but it is difficult to fabricate compared with the other materials being tested.

A high-temperature, single-stage mixer-settler is being tested to evaluate possible applications of multistage units for pyrochemical processing of fast breeder reactor fuels and for other chemical and metallurgical uses (see ANL-7595). Recently, the diameter of the top section of the agitator-pump was reduced to lower the output of the pump. This change also provides greater annular clearance between the pump and the upper portion of the mixing chamber, and improves the pump's tolerance to insoluble materials in the salt and metal phases.

Experiments are currently being conducted with metal and salt to establish the relationships between pumping rate, pump speed, metal-salt ratio, and hydraulic head of the metal and salt phases.

The unit is performing very satisfactorily. Repeated thermal cycling has had no adverse effect on the components and essentially no vaporized metal or salt has accumulated in the upper regions of the furnace vessel. Stage-efficiency experiments will be made next.

Fig. III.D.1. Relative Corrosion Resistance of Various Candidate Materials for Pyrochemical Processing

(iii) Laboratory Investigations of Head-end Process (I. Johnson)

Last Reported: ANL-7581, p. 107 (June 1969).

A head-end step suggested for processing LMFBR oxide fuel consists of pyrochemical means for decladding the fuel, reducing the fuel oxide, and separating plutonium from precipitated uranium and some fission products. Dissolution of the plutonium-containing reduction alloy in acid

may provide a suitable feed for existing plants for processing LWR fuels. The behavior of fission product iodine in this procedure is of interest because of the limited capacity of solvent-extraction processes to accommodate iodine. Even though the iodine in the fuel may be removed by the pyrochemical-processing steps, precursors of ^{127}I , ^{129}I , and ^{132}I (namely, ^{127}Sb , $^{129\text{m}}\text{Te}$, ^{129}Te , and ^{132}Te) may remain in the plutonium reduction alloy.

In calculations of the growth of iodine from antimony and tellurium precursors, 30-day cooling of Atomics International reference LMFBR fuel prior to decladding was assumed, as well as complete removal of fission product iodine and no removal of antimony and tellurium in the decladding and oxide-reduction steps. Under these conditions, the major source of radioactive iodine will be the decay of ^{132}Te to form ^{132}I ($t_{1/2} = 2.28$ hr). Calculations indicate that 50 hr after initial removal of iodine, ~ 32 Ci of ^{132}I per kilogram of plutonium will have grown into the Pu-Sb-Te solution. In comparison, in 150-day-cooled LWR fuel, ~ 0.35 Ci of iodine activity is present per kilogram of plutonium; the latter value may represent the maximum capacity for separation of radioiodine of current solvent-extraction processes. Approximately 23 days of additional cooling of the Pu-Sb-Te-I mixture from 30-day-cooled LMFBR fuel would reduce the iodine activity to that in 150-day-cooled LWR fuel. Thus, the iodine content of the LMFBR feed could be made compatible with the current aqueous-process technology by removing tellurium during the pyrochemical decladding and reduction steps, or by using a 53-day cooling period, or by modifying the aqueous process to increase its tolerance for radioiodine by a factor of 100.

(iv) Extraction-process Supporting Studies (I. Johnson)

Last Reported: ANL-7577, p. 173 (April-May 1969).

The effect of calcium concentration on the solubility of zirconium in a liquid Cu-Mg-Ca reduction alloy is being investigated to provide information on the behavior of fission product zirconium in pyrochemical processes. Previous experimental data (see Progress Report for February 1969, ANL-7553, p. 101) have shown that calcium suppresses the solubility of zirconium in the Cu-Mg-Ca alloy.

Partial analytical data from recent experiments indicate that an insoluble zirconium-calcium or zirconium-calcium-copper intermetallic compound forms as an equilibrium solid phase in the reduction alloy. Additional analyses are being made to clarify the phase relations in this system.

2. General Chemistry and Chemical Engineering--Research and Development

a. Thermophysical Properties

- (i) Oxygen Gradients, Total Vapor Pressures, and Oxygen Potentials in Reactor Fuels (P. E. Blackburn and A. J. Becker)

Last Reported: ANL-7577, p. 177 (April-May 1969).

Work is continuing on the assembly of components of the transpiration apparatus that will be used for measuring both oxygen potentials and total pressures over PuO_{2-x} . Initial temperature measurements within the furnace, taken under experimental conditions, indicated that a thermal gradient exists in the hot zone between the sample position and the bottom of the furnace tube. Since the measurements of the latter will be used in obtaining sample temperatures during an actual run, the difference in temperature between the two positions is being established.

Currently, with the argon carrier gas being circulated in the transpiration apparatus, measurements of the background partial pressures of water and oxygen are in progress.

- (ii) Total Effusion of Pu-O and U-Pu-O System (P. E. Blackburn and R. K. Edwards)

Last Reported: ANL-7577, p. 178 (April-May 1969).

The effusion apparatus, previously used to determine the congruently vaporizing composition of urania as a function of temperature, has been installed in a glovebox so that effusion studies of plutonium-bearing materials may be carried out. The new apparatus configuration incorporates a quadrupole mass spectrometer and a vacuum microbalance. The mass spectrometer and such internal components as the Knudsen cell mounting device and the induction heating coil have now been installed.

Testing of the apparatus is currently underway. Initial heating tests indicate that the possible adverse electrical interaction between the radiofrequency fields of the induction heater coil and the quadrupole probe of the mass spectrometer is negligible. Effusion experiments with nonplutonium-bearing materials will begin following critical alignment and calibration of the mass spectrometer and microbalance. Plutonium studies will begin after full plutonium capability for the glovebox has been achieved.

3. Sodium Chemistry--Research and Development

a. Fundamental Properties and Radioactive Contaminant Behavior

(i) Characterization of Oxygen- and Hydrogen-bearing Compounds in Sodium (F. A. Cafasso)

Last Reported: ANL-7577, p. 177 (April-May 1969).

Investigation of sodium systems by microscopy has been undertaken to determine the morphology of sodium oxide crystallites and the kinetics of their growth in sodium. Experimentation on slicing and chemical etching of sodium led to the following observations: (1) slices of sodium, thin and smooth enough for microscopy, can be prepared by microtoming specimens that are cooled to liquid nitrogen temperature, and (2) acetone will serve as an adequate etchant for preliminary observations, but better methods of etching must be found before definitive measurements can be made. Accordingly, cathodic etching of sodium is now being explored.

(ii) Surface Phenomena in Liquid Sodium (F. A. Cafasso)

(Final report)

Last Reported: ANL-7577, p. 177 (April-May 1969).

The role of surface diffusion in the transport and corrosion of structural materials in liquid sodium has not been investigated previously. A study of this effect in α -iron by the technique of grain-boundary grooving has been completed. Polished specimens of α -iron were exposed to liquid sodium at 800°C, within iron capsules, for up to 200 hr. The profiles of the grain-boundary grooves that developed on the polished surfaces were determined with a Zeiss double-beam interference microscope. Both the groove profiles and their rate of development can be analyzed according to the theory of Mullins* to determine the mechanism of diffusion (volume or surface transport) and the diffusion coefficient.

Fig. III.D.2. Profile of a Grain-boundary Groove

Groove profiles, as shown in Fig. III.D.2, are conveniently characterized through measurement of the relative ridge height of the groove, h/d , where h is the height of the groove ridge and d is the depth of the groove. According to Allen,** the value of h/d is 0.149 for volume diffusion through the solid or liquid phase and 0.208 for surface or interfacial

*Mullins, W. W., J. Appl. Phys. 28, 333 (1957); Trans. Met. Soc. AIME 218, 354 (1960).

**Allen, B. C., Trans. Met. Soc. AIME 236, 915 (1966).

Fig. III.D.3. Relative Ridge Heights of α -Iron Grain-boundary Grooves Formed in Liquid Sodium at 800°C

diffusion. At the time of the last report (see ANL-7577), h/d had been measured for only a few grooves, and the preliminary findings suggested a mechanism of volume diffusion. Since then, interferometric examinations of 59 different grooves have been made. The h/d values are shown on the histogram in Fig. III.D.3. The distribution has a most frequently observed value in good agreement with that expected for surface diffusion.

The diffusion mechanism can also be identified by the time dependence of the groove width w , which is the distance between the maxima of the groove, as shown in Fig. III.D.2. Mullins has shown that for volume diffusion

$$w = 5.0(At)^{1/3}, \quad (1)$$

whereas for surface diffusion

$$w = 4.6(Bt)^{1/4}, \quad (2)$$

where t is time, and A and B are constants at a given temperature. The width of the largest groove on each of seven specimens annealed at 800°C was used in the kinetic analysis. A log-log plot of w versus t is shown in Fig. III.D.4. A least-squares analysis of the data yielded a slope of 0.22 with a standard deviation of ± 0.04 , in reasonable agreement with the exponent of $1/4$ which Eq. (2) indicates is appropriate for surface diffusion. A value of $B = 5.3 \times 10^{-21} \text{ cm}^4/\text{sec}$ was also obtained.

The coefficient B in Eq. (2) was shown by Mullins to be

$$B = D_{SL} \nu \gamma_{SL} \Omega^2 / kT, \quad (3)$$

where D_{SL} is the interfacial diffusion coefficient, ν is the surface atom concentration, γ_{SL} is the interfacial tension, Ω is the atomic volume, k is the Boltzmann constant, and T is the absolute temperature. In their study of the grain boundary grooving of α -iron in vacuum, Blakely and Mykura* calculated a surface diffusion coefficient of $D_{SV} = 5 \times 10^{-7} \text{ cm}^2/\text{sec}$ at 800°C on the basis of an atomic spacing of 2.5 Å and a surface tension

Fig. III.D.4. Maximum Groove Width vs Time for α -Iron Grain-boundary Grooves Formed in Liquid Sodium at 800°C (Slope = 0.22 ± 0.04)

*Blakely, J. M., and Mykura, H., *Acta Met.* **11**, 399 (1963).

of $\gamma_{SV} = 2000 \text{ erg/cm}^2$. Using the same atomic spacing and surface tension values here gives $\nu = 2^{-1/6} \Omega^{-2/3}$, $\Omega = 7.8 \times 10^{-24} \text{ cm}^3/\text{atom}$, and $\gamma_{SL} = 2000 \text{ erg/cm}^2$. By inserting the appropriate values in Eq. (3), a surface diffusion coefficient of $D_{SL} = 3 \times 10^{-6} \text{ cm}^2/\text{sec}$ is obtained for α -iron grooving in liquid sodium at 800°C .

In summary, the results indicate that surface diffusion is an important transport mechanism in corrosion by liquid sodium, and that for α -iron at 800°C surface diffusion proceeds more rapidly in liquid sodium than in vacuum.

PUBLICATIONS

Irradiation Testing (Pulse Conditions) of the Ternary Fuel System for the Power Burst Facility

R. J. Beals and R. S. Kern*

J. Am. Ceram. Soc. 52, 355-358 (July 1969)

Sealing Large Ultrahigh-Vacuum Flanges with Polytetrafluoroethylene Gaskets

P. M. Danielson

J. Vacuum Sci. Technol. 6(3), 425-427 (1969)

A Foreline Trap for Contamination-Free Roughing

P. M. Danielson and F. C. Mrazek

J. Vacuum Sci. Technol. 6(3), 423-425 (1969)

Law of Maxima in Species Partial Pressures for Vaporization Equilibria in Two-Component Systems

R. K. Edwards

High Temperature Sci. 1(2), 232-237 (July 1969)

Electronic Absorption Spectra and the Nature of Dilute Solution of Alkali Metals in Alkali Halides

D. M. Gruen, Michael Krumpelt, and Irving Johnson

Molten Salts, Ed. Gleb Mamantov, Marcel Dekker, Inc., New York, 1969, pp. 169-188

Some Simple Techniques to Prepare Powder Samples for Spark Source Mass Spectrometric Analysis

P. K. Hon

Anal. Chem. 41, 1148 (July 1969)

Ultrasonic Excitation of Thermoluminescent Lithium Fluoride

J. Kastner, R. H. Selner, C. M. Paden, and B. G. Oltman

Health Physics 16, 803-804 (1969)

*Phillips, Idaho.

Retorting Unit for Recovery of Uranium from Zinc-Magnesium Solutions

J. F. Lenc, W. E. Miller, G. J. Bernstein, A. L. Chandler, R. C. Paul,
and E. F. Johnston

ANL-7503 (April 1969)

An Investigation of the Level Spins of ^{59}Co Using the (n,n',γ) Reaction

V. C. Rogers, S. C. Mathur,* and P. S. Buchanan**

Bull. Am. Phys. Soc. 14, 852 (August 1969) Abstract

Colorimetric Determination of Zirconium with 1-(2-pyridylazo)-2-naphthol

L. E. Ross, V. M. Drabek, and R. P. Larsen

Talanta 16(6), 748-750 (1969)

A Small Cylindrical Separatory Funnel and Rack

L. E. Ross and R. A. Juvinall

J. Chem. Educ. 46, 322 (May 1969)

Solubilities of Nitrogen Gas and Sodium Cyanide in Liquid Sodium

E. Veleckis, K. E. Anderson, F. A. Cafasso, and H. M. Feder

Proc. Intern. Conf. on Sodium Technology and Large Fast Reactor
Design, Argonne National Laboratory, November 7-9, 1968;

ANL-7520, Part I, pp. 295-298

The following appeared as Abstracts of Papers Presented at the 158th Am.
Chem. Soc. Mtg., New York, September 8-12, 1969

Distribution of Alpha and Gamma Emitting Nuclides in a Fast Reactor Irradiated $\text{UO}_2\text{-PuO}_2$ Fuel

M. D. Adams

NUCL-52

Electron Microprobe Studies of the Migration of Elements in Irradiated Oxide Fuels

C. E. Crouthamel, N. R. Stalica, C. E. Johnson, and C. A. Seils

NUCL-47

The Role of Nuclear Chemistry in Fast Reactor Development

N. D. Dudey

NUCL-36

EBR-II Spectrum-Averaged Cross Sections

R. R. Heinrich, N. D. Dudey, and M. Foster

NUCL-40

X-Ray Spectrometric Determination of Fission Product Rare Earths. Application to the Measurement of Burnup in Nuclear Fuels

R. P. Larsen, R. V. Schablaske, R. D. Oldham, R. J. Meyer, and

M. I. Homa

NUCL-49

*Lowell Technol. Inst., Massachusetts.

**Texas Nuclear Corp.

Theory of Fast Reactor Cross Sections

P. A. Moldauer

NUCL-37

The following appeared in Nuclear Metallurgy, Vol. 15, Symp. on Reprocessing of Nuclear Fuels, Ames, Iowa, August 25-27, 1969. USAEC Report CONF-690801

The Solubility of Uranium and Plutonium in Liquid Alloys

I. Johnson

pp. 547-564

The Potential of the Fluoride Volatility Process for Fast Breeder Reactor Fuels

A. A. Jonke, N. M. Levitz, and M. J. Steindler

pp. 231-240

Uranium and Plutonium Purification by the Salt Transport Method

J. B. Knighton, I. Johnson, and R. K. Steunenberg

pp. 337-362

Contribution to the Plutonium-Magnesium Phase Diagram

W. Knoch, J. B. Knighton, and R. K. Steunenberg

pp. 535-546

Containment Materials for Pyrochemical Processes

M. L. Kyle, R. D. Pierce, and V. M. Kolba

pp. 433-452

Engineering-Scale Fluoride Volatility Studies on Plutonium-Bearing Fuel Materials

N. M. Levitz, E. L. Carls, D. E. Grosvenor, G. J. Vogel, and

I. E. Knudsen

pp. 211-230

Multistage Contactors for Liquid Metal-Salt Extraction

R. D. Pierce, W. E. Miller, J. B. Knighton, and G. J. Bernstein

pp. 511-533

Laboratory Development of the Fluoride Volatility Process for Oxidic Nuclear Fuels

M. J. Steindler, L. J. Anastasia, L. E. Trevorow, and

A. A. Chilenskas

pp. 177-210

Status of the Salt Transport Process for Fast Breeder Reactor Fuels

R. K. Steunenberg, R. D. Pierce, and I. Johnson

pp. 325-335

EBR-II Skull Reclamation Process

I. O. Winsch, R. D. Pierce, G. J. Bernstein, W. E. Miller, and

L. Burris, Jr.

pp. 297-324

IV. NUCLEAR SAFETY RESEARCH AND DEVELOPMENT

A. LMFBR Safety--Research and Development

1. Accident Analysis and Safety Evaluation (G. J. Fischer)

Last Reported: ANL-7581, pp. 117-118 (June 1969).

a. Special Systems Analysis

A recent experiment (S-3) on fuel failure behavior during transient meltdown in a sodium-filled piston autoclave (see Progress Report for February 1969, ANL-7553, p. 113) has been analyzed using the fast reactor accident study code SASIA. The method of analysis is similar to one described in ANL-7581. In the present analysis, data from recent high-temperature measurements of the specific heat of uranium dioxide are used rather than the low-temperature extrapolated data used earlier.

The analysis of the five-pin autoclave experiment is based on an equivalent single-pin configuration. Due to the code requirements, stagnant sodium was replaced by slowly circulating sodium. The fuel pin was irradiated in the TREAT transient, which was equivalent to an energy input of 1920 J/g- UO_2 in the pin. Considering the fuel pin to be cooled by an equivalent amount of liquid sodium, the peak fuel temperature was calculated to be 4100°C; the maximum cladding temperature was calculated to be within 200°C of its melting point. If the amount of sodium available to the pin under consideration is reduced by a factor of 2, the resulting peak cladding temperature approaches its melting point toward the end of the power transient. At this time the calculations indicate initiation of coolant boiling.

The cladding behavior is analyzed in terms of its permanent deformation. Figure IV.A.1 shows a plot of this quantity as a function of energy released in the pin. Although the cladding undergoes plastic flow even before any fuel melting occurs, the deformation is small. The major cladding deformation takes place after fuel melting starts. The calculated maximum deformation, occurring at the end of the transient, is found to be 5.8%. The mass fraction of molten UO_2 , as shown in the figure, increases very rapidly to 80%, corresponding to energy input of 1500 J/g- UO_2 , which is well beyond that required for full melting under adiabatic conditions.

The pin failure can be caused either by clad melting or the excessive cladding deformation. Failure due to clad melting does not appear to be the case since the maximum cladding temperature attainable during the transient is below the melting point. This argument is substantiated by the experimental observations of coolant temperature profiles. If the time of failure is assumed to be known accurately, the present study indicates

failure with 5.8% plastic deformation corresponding to energy release of 1900 J/g- UO_2 . At this time of failure, the expanded UO_2 radius is calculated to be 0.352 cm, equivalent to the room-temperature radius of 0.338 cm. This radius compares very well with the experimentally observed outer radius of the hollow fuel section of 0.336 cm. It is possible to visualize the clad melting after the end of the transient by further heating of the clad from the fuel. It is emphasized that no axial motion of molten fuel was allowed in these calculations. Axial motion of molten fuel would result in a smaller strain on the cladding.

Fig. IV.A.1.

Plastic Deformation of the Clad and the Fraction of UO_2 Melted as a Function of the Energy Release in the Fuel

2. Coolant Dynamics

a. Sodium Expulsion (R. M. Singer and R. E. Holtz)

Last Reported: ANL-7581, pp. 121-122 (June 1969).

(i) Static Expulsion Tests

(a) Collection and Analysis of Data from Initial System.

Figure IV.A.2, a plot of data obtained during sodium expulsion, is a one-dimensional transient map of the liquid-vapor interface. The initial expulsion and subsequent reentry ~0.2 sec later are clearly illustrated. The inception of boiling is seen to have occurred ~5-6 cm above the top of the heated zone; essentially complete voiding above the heater occurred within ~20 msec. The vapor slowly advanced into the heated zone (the lower end of which is blocked). Figure IV.A.2 also shows the temperature profile of the liquid at boiling inception.

Figure IV.A.3 shows the size of the transient vapor bubble (or, equivalently, the liquid-column displacement) as measured in sodium; also included are data obtained using water and methanol in which

Fig. IV.A.2

One-dimensional Transient Map of Liquid-Vapor Interface during Sodium Expulsion Test in Which Liquid Superheat ΔT_L Was 57°C , Saturation Temperature T_s Was 850°C , Wall Heat Flux q_w Was 66.0 w/cm^2 , Height of Liquid Column above Heater L_0 Was 94 cm , and Height of Heated Zone L_h Was 7.0 cm

Fig. IV.A.3. Size of Transient Vapor Bubbles in High-void-fraction Two-phase Mixtures of (a) Sodium, (b) Water, and (c) Methanol. P_g is pressure of gas blanket; other symbols are as defined for Fig. IV.A.2.

the expanding vapor region was a high-void-fraction two-phase mixture. The use of a "displacement group" (the ratio of the transient liquid-column displacement to the pressure difference corresponding to the incipient-boiling superheat and the liquid-column height and blanket pressure) apparently correlates the data from a wide range of conditions quite well. This result strongly indicates that, in the range of variables studied, the vapor growth rate is controlled by the inertia of the liquid. The excellent agreement among the various liquids offers an excellent argument for using non-metallic fluids to simulate liquid metals in experiments of complex geometry.

(b) Preparation of New-geometry Test Section. Calibration of the sensors installed in the new static sodium-expulsion apparatus is continuing. An attempt is being made to permit measurement of the thickness of the transient liquid film remaining on the heated walls during the observed single-bubble ejection process.

(c) Analysis of Data and Interpretation in Terms of Physical Models. The simple single-bubble inertia model that overpredicts the observed behavior at times greater than about 50 msec is being modified to take into account the nonconstancy of the driving pressure differential. The results of this model should provide a simple relationship for the transient bubble size as well as further support for the observed voiding mechanism.

(ii) Forced-convection Expulsion Tests

(a) Preparation of Transient Test Loop. Except for the heater section and flowmeter, all loop components and piping have been assembled. The heater is being assembled; the flowmeter has been built and will be installed in the system after the rest of the system has been checked for leaks.

A clean room was built to house the data system and most of the controls for the system. The data system has been received and will be checked before installation in the clean room.

b. Sodium Simulations (M. A. Grolmes and H. K. Fauske)

(i) Expulsion of Nonmetallic Fluids from Multiple-pin Geometries (Static Tests)

Not previously reported.

Experiments have been initiated on the expulsion of superheated Freon-11 from multipin channels to determine if analytical models based on single-channel expulsion experiments can be applied to multipin

geometries. Single-channel expulsion studies have indicated a slug-type expulsion process resulting from the growth of a single bubble (see Progress Report for March 1969, ANL-7561, p. 93). Preliminary results of the rapid depressurization of Freon-11 in a channel with seven 6-mm-OD pins also indicate a one-dimensional or slug-type voiding pattern that develops within approximately one channel diameter from the nucleation site. Additional studies underway include observations in a 19-pin glass assembly.

3. Core Structural Safety (C. K. Youngdahl)

Last Reported: ANL-7591, pp. 122-124 (June 1969).

a. Dynamic Plasticity Analysis of Circular Shells

A parameter study is being performed to determine the plastic deformation of a circular cylindrical shell loaded by a dynamic pressure that varies both axially and with time. The axial load shapes being considered are of the family (see Progress Report for January 1968, ANL-7419, pp. 154-157),

$$\phi_{\gamma}(z) = \frac{\gamma + 1}{a\gamma} \left[1 - \left(\frac{z}{a} \right)^{\gamma} \right]; \quad 0 < \gamma < \infty,$$

and the pulse shapes being used for the parameter study are rectangular, triangular, exponential decay, linear decay, and half-sine.

For an initial instantaneous jump in the pulse it has been found that (a) for $\gamma = 1$ (linear axial shape) the motion always starts in Phase 1; (b) for $\gamma < 1$ (concave-up axial shape) the motion may start in either Phase 1 or Phase 2, i.e., there may be a hinge band at the center of the load; (c) for $\gamma > 1$ (convex-up axial shape) the motion may start in Phase 1 or Phase 3, i.e., there may be outer hinge bands.

The results of the study thus far indicate that, for any given axial shape, the proposed equivalence parameters (the impulse and effective load) provide an excellent means of correlating final plastic deformations produced by different pulse shapes.

4. Materials Behavior and Energy Transfer

a. Segregation of Plutonium in Fast Reactor Fuels under a Thermal Gradient (M. G. Chasanov)

Last Reported: ANL-7577, p. 196 (April-May 1969).

Experimental work to determine the extent of migration and segregation in mixed uranium-plutonium fuels under a thermal gradient has

been completed. Current activities chiefly involve data analyses; a report will be prepared summarizing the results of these studies.

Microprobe analyses of two mixed-carbide fuel pellets (see ANL-7577) have been completed. These pellets contained 4.61 wt % carbon, 81.0 wt % uranium, and 14.4 wt % plutonium. One pellet was heated for 437 hr in a thermal gradient of $\sim 700^{\circ}\text{C}/\text{cm}$ (temperature of the top surface of the pellet was $\sim 2000^{\circ}\text{C}$). The second pellet was heated for 460 hr under a similar thermal gradient; the latter specimen was heated inside an inverted tungsten crucible, which apparently served as a barrier to loss of plutonium by vaporization. The tungsten crucible was similar to those used in the mixed-oxide fuel-migration studies (see Progress Report for April 1968, ANL-7445, p. 141). The pellet that had not been covered during heating showed marked losses of plutonium in the upper (hotter) regions of the sample, whereas the covered pellet showed little plutonium loss. Ceramographic examination of these samples is in progress.

5. Fast Reactor Safety Test Facility Study (C. N. Kelber)

Last Reported: ANL-7595, pp. 118-120 (July 1969).

a. Program Definition and Justification

A letter report to RDT on preliminary judgement of the need for "whole-subassembly" and "whole-core" tests was transmitted to RDT.

Comments on the "Preliminary (Phase I) Draft of the Project Report: Studies of Safety Test Facilities, Volume 1, Program" have been received from all but one of the industrial and laboratory correspondents.

The 1000-MWe LMFBR Design Study reports were reviewed in order to determine the major safety problems and design uncertainties as they relate to the ability of the designers to predict performance under various abnormal conditions. Although there was a lack of unanimity in the identification and solutions to fast reactor fuel failure, most of the plant designers were concerned about the inability to predict, with accuracy, the mechanisms of fuel-failure propagation, especially from subassembly to subassembly. Because of lack of a good quantitative understanding of many of the basic reactions and mechanisms and the various interactions which contribute to the total picture of fuel-failure propagation, it was often necessary to make pessimistic assumptions which probably would not have had to be made if the fuel-failure propagation and core-meltdown phenomenon were better understood.

Various simplified codes were used to describe pin failure and pin-to-pin failure propagation. In some cases the designers took the

position that, in the absence of either good empirical information or a reliable computer code, accidents involving major damage to the core required the assumption of complete interaction of the molten fuel and the sodium coolant in the core. These designers felt that this extremely pessimistic assumption had to be made for the safety analysis since no other position could be justified at this stage of development of fast reactor safety and technology.

b. Facility Definition and Utilization

A preliminary neutronic survey described earlier has been extended to compute typical reactivity coefficients for typical driver cores with 10-MW (steady-state) loops containing typical LMFBR fuel (see Tables IV.A.1 and IV.A.2). The test loop fuel was, however, enriched to 25% ^{235}U in the UO_2 for this analysis.

TABLE IV.A.1. Nominal
Outer Radii (cm)

Region		Region	
Test	7.875	Core Zone 3	48
Loop Wall	15	Core Zone 4	53
Core Zone 1	33	Reflector	93
Core Zone 2	43		
(Equivalent Bare Height = 140)			
(Actual Core Height = 110)			

TABLE IV.A.2. Basic Compositions
(Volume Fractions)

Region	UO_2	PuO_2	SS	Na	Ni
Test	0.40664	0.05336	0.18	0.36	
Loop			0.4	0.4	
Core	0.4		0.16	0.38	
Reflector				0.1	0.9

Four different compositions (see Table IV.A.3) were studied. The zone thicknesses were varied in one dimension to achieve criticality, and the Doppler coefficient was computed by k-calculation. For the most

TABLE IV.A.3. Core Variations (Volume Fractions)

Variation	Region			
	1	2	3	4
1	BeO = 0.019	0.2907	0.04485	0.06094
	U-235 = 0.078	0.0962	0.115	0.1288
	U-238 = 0.3628	0.3343	0.30015	0.27026
2	0	0.03634	0.05175	0.07187
	0.078	0.0662	0.115	0.1288
	0.3818	0.32706	0.29325	0.25833
3	0.038	0.05814	0.0897	0.12188
	0.078	0.0962	0.115	0.1288
	0.3438	0.3053	0.2553	0.20932
4	0	0.07268	0.1035	0.14374
	0.078	0.0962	0.115	0.1288
	0.3818	0.29072	0.2395	0.18746

favorable case, the feedback from meltdown and compaction of the upper part of the test loop was determined from two-dimensional k-calculations. Feedback from compaction was also determined for a 50% enriched fuel in the test loop.

The most favorable Doppler coefficient ($-T dk/dT$) computed (see Table IV.A.4) was 7.2×10^{-3} (for comparison SEFOR: 8.5×10^{-3}).

TABLE IV.A.4. Doppler Coefficients ($-T dk/dT$)

Variation	
1	6.6×10^{-3}
2	6.12×10^{-3}
3	7.17×10^{-3}
4	6.8×10^{-3}
SEFOR: 8.5×10^{-3}	

For $T_0 = 900^\circ\text{K}$ and $T_1 = 2100^\circ\text{K}$, $\Delta k = 0.00612$.

For the same configuration the computed Δk for compaction of the upper part of the test loop was 0.00778. For a T_0 of 300°K , the Doppler feedback is $-0.014 \Delta k$. If the test loop is enriched to 50% U-235 the feedback from compaction is estimated at $+0.025 \Delta k$.

Thus, a large loop with a modest power-density ratio of ~ 1.4 with respect to the driver may be marginally fail safe with respect to steady-state experiments, since

the Doppler coefficient is normally only part of the shutdown feedback. For pulsed experiments (cold start) a slightly larger power-density ratio may be available.

The close competition between the Δk from compaction and that available from the Doppler effect indicates that nuclear feedback effects will play a determining role in establishing facility characteristics needed for the conduct of large loop experiments.

A compilation of design and performance data for existing reactors capable of performing fuel-failure experiments has been started. The source of information for this compilation includes both a literature search and trip reports. A preliminary draft will be issued.

At the lower neutron energies present in thermal reactors perturbations in performance due to self-shielding, flux depression, etc., become pronounced. However, in a thermal reactor irradiation facility, the test section can be decoupled from the driver core by means of neutron filters and rectifiers. This decoupling feature greatly enhances the safety of the experiment by reducing feedback from the test section to the high-performance driver core, thus reducing the possibility of damage to the driver fuel.

Further assessment of the thermal performance of various sizes of test bundles will be continued to determine the net effect of flux depression in the pin, self-shielding, etc., on the temperature distribution, heat transfer, and other phenomena that contribute to the overall performance of the test

specimen. An attempt will be made to appraise quantitatively the effectiveness of tests in a thermal reactor to simulate performance in a fast reactor environment.

Concurrent with this performance evaluation and comparison, a safety analysis has been started to evaluate the safety problems associated with conducting fast reactor tests in the type of thermal reactors currently available.

A set of constants for the Himpan equation of state for sodium has been found which can be recommended for use on an interim basis. They give good agreement with experimental specific volume data. The Himpan equation is

$$\left[P + \frac{a}{(v-b)(Tv-c)} \right] (v-d) = RT.$$

The recommended values for the constants are

$$\begin{aligned} a &= 2.23910 \times 10^7 \quad (\text{m}^5\text{-}^\circ\text{K}/\text{kg s}^2) \\ b &= 1.97235 \times 10^{-5} \quad (\text{m}^3/\text{kg}) \\ c &= -8.86664 \quad (\text{m}^3\text{-}^\circ\text{K}/\text{kg}) \\ d &= 1.09038 \times 10^{-3} \quad (\text{m}^3/\text{kg}) \\ R &= 361.652 \quad (\text{J}/\text{kg-}^\circ\text{K}) \end{aligned}$$

These give a critical point of

$$\begin{aligned} P_c &= 5.282 \times 10^7 \quad (\text{N}/\text{m}^2) \\ T_c &= 2730 \quad (^\circ\text{K}) \\ V_c &= 5.500 \times 10^{-3} \quad (\text{m}^3/\text{kg}) \\ Z_c &= 0.2942 \end{aligned}$$

A suitable vapor pressure law is

$$\begin{aligned} \log_e P_s(T) &= 26.1553 - (12818.5/T) - 0.5 \log_e T \quad (T < 1145) \\ &= 26.9100 - (12767.8/T) - 0.61344 \log_e T \\ &\quad (1145 < T < 1645) \\ &= 10.6121 + (7005.72/T) - 1.05284 \times 10^7/T^2 \\ &\quad + 2.20392 \times 10^{-3}T \quad (1645 < T < T_c) \\ &\quad (T \text{ in } ^\circ\text{K}, P_s \text{ in N}/\text{m}^2). \end{aligned}$$

The formulae for the first two ranges (that is, $T < 1645^\circ\text{K}$) are those recommended by Golden and Tokar. The formula for $T > 1645^\circ\text{K}$ has been chosen to be consistent with the others (i.e., P_s and dP_s/dT are continuous at $T = 1645^\circ\text{K}$) and also to be consistent with the Himpan equation at the critical point [i.e., $P_s(T_c) = P_c$, and $(dP_s/dT)_{T=T_c} = (\partial P/\partial T)_v$ evaluated from the Himpan equation at the critical point].

The agreement with Golden and Tokar's fit to Stone's saturated-phase specific volume data (temperatures below 1800°K) is good (5% or less error for the liquid, 15% or less for the vapor). Above 1800°K the agreement with Dillon's data for the saturated-liquid specific volume is good (4% or less error). The agreement for the vapor phase in this temperature range is not good (up to 100% error), but Dillon's experimental values are very scattered, making comparison difficult and possibly misleading.

6. Violent Boiling

a. Violent Boiling with Molten Fuel and Sodium (D. R. Armstrong)

Last Reported: ANL-7548, p. 129 (Jan 1969).

(i) Pressure-generation Experiments by Dropping Molten Material into Coolant. A series of trial experiments using a 100-kW induction generator and an inert-atmosphere furnace chamber have been made to demonstrate melting of UO_2 in preparation for experiments involving UO_2 -Na interaction. The furnace chamber is a water-cooled stainless steel cylinder (12 in. in diameter by 26 in. long) equipped with two quartz windows and a coaxial rf power lead. In the preliminary trials, a cylindrical tungsten crucible (of $7/8$ in. OD and 2 in. high) containing ~ 40 g UO_2 was placed concentrically within a single-layer cylindrical work coil made of $1/4$ -in.-square silver-plated copper tubing.

In the initial test of the system, severe arcing occurred between the coil and crucible at a crucible temperature of $\sim 2200^\circ\text{C}$. All crucible temperatures were measured with an optical pyrometer sighted through one of the quartz windows.

A second trial was made after the system was modified by electrically isolating the crucible, using a ZrO_2 support rod, and by increasing the diameter of the work coil. The maximum temperature achieved in this test was 2920°C . No arcing between coil and crucible was observed, although there was indication of arcing somewhere in the system. An examination of the crucible after the trial showed that the UO_2 had been melted with the exception of a crust $\sim 3/8$ in. thick.

Additional trials employed a tungsten radiation shield above the crucible and an aluminum shield to protect the window flanges from

radiant energy. The severity of the arcing increased during these tests and overloaded the generator, at which time the crucible was at 2820°C. Subsequent examination of the crucible showed that the UO_2 had not melted, thus confirming the measured temperatures, i.e., UO_2 (M. P. = 2850°C) was molten at a measured temperature of 2920°C and remained solid at 2820°C.

The equipment was disassembled after this test, and the site of the arcing was located on the inside of the coaxial power lead. The lead was redesigned to improve the insulation and the transfer efficiency.

The redesigned system gave slightly better results during the next trial. A maximum crucible temperature of 3050°C was reached. Although all of the UO_2 was melted, a thin ($<1/8$ in.) polycrystalline crust remained at the upper surface of the melt. This crust possessed little mechanical strength and appeared as a packed mass of crystal grains of about $1/16$ - $1/32$ -in. diameter.

While the apparatus for dropping molten UO_2 into sodium is being installed in the furnace chamber, further tests will be made using other coil designs to determine the optimum heating arrangement.

(ii) Piston Autoclave Experiment in TREAT. A group of five stainless steel-clad UO_2 fuel elements in a sodium-filled piston autoclave (experiment S-4) was subjected to a transient irradiation and neutron radiographed. Preliminary analysis of the data indicates that the fuel received an energy input of about 700 cal/g of UO_2 . Short-duration pressure pulses with maximum amplitudes up to 1700 psi were recorded. Post-transient neutron radiographs showed that the fuel was widely distributed. In a previous experiment (S-3) with an energy input of 460 cal/g, very little axial fuel movement occurred. (See Progress Report for February 1969, ANL-7553, p. 113.)

PUBLICATIONS

Slow-Neutron Scattering by Molecular Liquids

A. K. Agrawal and S. Yip*

Nucl. Sci. Eng. 37, 368-379 (1969)

Operating Experience with TREAT

J. F. Boland

Trans. Am. Nucl. Soc. 12(Suppl.), 15 (Oct 1969) Abstract

Thermoelastic Vibrations of Thick Elastic Anisotropic Shells

G. Cinelli

Proc. 11th Midwestern Mechanics Conf., Ames, Iowa,
August 18-20, 1969. Iowa State University, Ames, 1969, Vol. 5,
pp. 451-468

Propagation Velocity of Pressure Waves in Gas-Liquid Mixtures

R. E. Henry, M. A. Grolmes, and H. K. Fauske

Cocurrent Gas-Liquid Flow, Ed. E. Rhodes, Plenum Press,
New York, 1969, pp. 1-18

PUBLICATIONS--General

Proceedings of the International Conference on Sodium Technology and
Large Fast Reactor Design, November 7-9, 1968

Part I. Sessions on Sodium Technology

Part II. Sessions on Large Fast Reactor Design

ANL-7520

The Pressure Recovery of a One-component Two-phase Flow in a Two-
dimensional Diffuser

Hugo P. Korstanje

ANL-7504 (January 1969)

*Massachusetts Institute of Technology.