270
6/28/68 leg
ANL-7299

MASTER

ANL-7299

Argonne National Laboratory

ANNUAL PROGRESS REPORT FOR 1966 METALLURGY DIVISION

The facilities of Argonne National Laboratory are owned by the United States Government. Under the terms of a contract (W-31-109-Eng-38) between the U. S. Atomic Energy Commission, Argonne Universities Association and The University of Chicago, the University employs the staff and operates the Laboratory in accordance with policies and programs formulated, approved and reviewed by the Association.

MEMBERS OF ARGONNE UNIVERSITIES ASSOCIATION

The University of Arizona
Carnegie Institute of Technology
Case Institute of Technology
The University of Chicago
University of Cincinnati
Illinois Institute of Technology
University of Illinois
Indiana University
Iowa State University

The University of Iowa
Kansas State University
The University of Kansas
Loyola University
Marquette University
Michigan State University
The University of Michigan
University of Minnesota
University of Missouri

Northwestern University
University of Notre Dame
The Ohio State University
Purdue University
Saint Louis University
Washington University
Wayne State University
The University of Wisconsin

LEGAL NOTICE

This report was prepared as an account of Government sponsored work. Neither the United States, nor the Commission, nor any person acting on behalf of the Commission:

A. Makes any warranty or representation, expressed or implied, with respect to the accuracy, completeness, or usefulness of the information contained in this report, or that the use of any information, apparatus, method, or process disclosed in this report may not infringe privately owned rights; or

B. Assumes any liabilities with respect to the use of, or for damages resulting from the use of any information, apparatus, method, or process disclosed in this report.

As used in the above, "person acting on behalf of the Commission" includes any employee or contractor of the Commission, or employee of such contractor, to the extent that such employee or contractor of the Commission, or employee of such contractor prepares, disseminates, or provides access to, any information pursuant to his employment or contract with the Commission, or his employment with such contractor.

Printed in the United States of America

Available from

Clearinghouse for Federal Scientific and Technical Information
National Bureau of Standards, U. S. Department of Commerce
Springfield, Virginia 22151

Price: Printed Copy \$3.00; Microfiche \$0.65

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency Thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

DISCLAIMER

Portions of this document may be illegible in electronic image products. Images are produced from the best available original document.

ANL-7299
Metals, Ceramics, and
Materials (TID-4500)
AEC Research and
Development Report

ARGONNE NATIONAL LABORATORY

9700 South Cass Avenue
Argonne, Illinois 60439

ANNUAL PROGRESS REPORT FOR 1966 METALLURGY DIVISION

Michael V. Nevitt, Director

Paul G. Shewmon, Associate Director

Haim H. Chiswik, Associate Director

LEGAL NOTICE

This report was prepared as an account of Government sponsored work. Neither the United States, nor the Commission, nor any person acting on behalf of the Commission:
A. Makes any warranty or representation, expressed or implied, with respect to the accuracy, completeness, or usefulness of the information contained in this report, or that the use of any information, apparatus, method, or process disclosed in this report may not infringe privately owned rights; or
B. Assumes any liabilities with respect to the use of, or for damages resulting from the use of any information, apparatus, method, or process disclosed in this report.
As used in the above, "person acting on behalf of the Commission" includes any employee or contractor of the Commission, or employee of such contractor, to the extent that such employee or contractor of the Commission, or employee of such contractor prepares, disseminates, or provides access to, any information pursuant to his employment or contract with the Commission, or his employment with such contractor.

The last three Annual Reports

ANL-6868	1963
ANL-7000	1964
ANL-7155	1965

TABLE OF CONTENTS

PART I ENGINEERING METALLURGY

A. Summary of Engineering Metallurgy	3
1. Fast-Reactor Metal Fuel Development and Fabrication	3
a. Development of U-Pu Zr Alloy Fuel Pins	3
b. Fabrication of U-Pu-Zr Test Fuel Elements	3
c. Phase Compositions in U-Pu-Ti System	3
d. Solid-State Reactions in U-Pu Zr System	3
e. Heat Content and Heat Capacity of U-15w/oPu-10w/oZr and U-15w/oPu-6w/oTi Alloys	3
f. Compatibility of U-Pu-Zr and U-Pu-Ti Alloys with Potential Jacket Materials	3
g. Fuel-Performance Studies of Uranium-Plutonium Alloys	3
h. Irradiation Behavior of Uranium-Plutonium Alloys	4
2. Fast-Reactor Oxide-Fuel Development and Fabrication	4
a. Commminution and Vibratory Loading of (U,Pu)O ₂ for Irradiation	4
b. Fuel-Performance Studies of Uranium-Plutonium Oxides	4
3. Fast-Reactor Carbide Fuel Development	4
a. Fabrication of Mixed Carbide Powders Derived from the Metal Alloy	4
b. Metal Additions to Hyperstoichiometric (U,Pu)C	4
c. Preparation of (U, 15w/oPu)C for Vibratorily-Compacted Fuel	4
d. Synthesis of Uranium-Plutonium Monocarbide Solid Solution by Reaction Sintering	4
e. Studies of Rate of Entry in Vibratory Compaction	5
f. Development of Process Equipment for Ceramic Fuels	5
g. Compatibility of Stoichiometric and Hyperstoichiometric Carbides with Potential Jacket Materials	5
h. Fuel-Performance Studies of Uranium-Plutonium Carbides	5
i. Irradiation Behavior of Vibratorily-Compacted UC-20w/oPuC Powders	5
4. Development of Doppler Element Loading Techniques	5
5. Fast-Reactor Jacket Development	5
a. Improvements in Consolidation and Fabrication of V-15w/oTi-7.5w/oCr	5
b. Alloy Development (Vanadium-Base Alloys)	6
c. Corrosion of Fuel-Jacket Materials for Sodium Cooled Reactors	6
d. Development of Refractory-Metal Alloys for Service in Oxygen-Contaminated Sodium	6
e. Exposure of V-20w/oTi Creep Specimens to Sodium	6
f. Uniaxial and Biaxial Creep of V-20w/oTi After Exposure to Sodium	6
g. Effect on Biaxial Creep of Exposing Type 304 Stainless Steel and Nb 1w/oZr to Sodium	6
h. Linear Thermal Expansion of Vanadium, Titanium, Chromium, and Some Vanadium-Base Binary and Ternary Alloys	6
i. Effect of Heat Treatment on the Uniaxial Creep of Vanadium Alloys	7
j. Uniaxial Tensile Properties of V-15w/oTi-7.5w/oCr at Constant Strain Rate	7
k. Stress and Temperature Dependence of the Activation Energy for the Creep of V-15w/oTi-7.5w/oCr	7
l. Irradiation of Fast-Reactor Jacket Materials	7
6. Zero-Power Fuel and Fuel Elements	7
a. Development of Zero Power Plutonium Reactor Fuel	7
b. Fabrication of Zero-Power Reactor Fuel from Plutonium Derived from Highly Irradiated Fuel	7
c. Properties of Zero-Power Uranium-Plutonium Metal Fuels	7
d. Flux Perturbation Elements	7
7. EBR II Assistance	8
a. Soret Effect in the Bismuth-Tin Eutectic Alloy	8
b. Irradiation Induced Changes in the Mechanical Properties of EBR II Fuel Jackets	8
c. Anomalous Swelling of Mark IA Fuel	8

8. Nuclear Safety	8
a. Radiation Measurements and Personnel Exposures Encountered during Fabrication of Reactivity-Coefficient Specimens	8
b. Penetration of Type 304 Stainless Steel and V-20w/oTi by Molten U-Pu-Zr and U-Pu-Ti Alloys	9
9. Development of Ceramic Fuels	9
a. Thermal Stability of Plutonium Ceramics	9
b. Uranium-Mixed Anion Systems	9
c. Electrical Properties and Electronic Configurations of the Actinide Metal Compounds with Nonmetals of Groups IV to VI	9
d. Thermal Conductivity and Heat Capacity of Actinide Compounds	9
e. (Th-U-Pu) Phosphide Bodies	10
f. Mechanical Properties of Uranium Compounds	10
10. Development of Thorium-Uranium and Thorium-Uranium-Plutonium Fuels	10
a. Phase Studies	10
b. Irradiation Behavior	10
11. Experimental Irradiation of Fuels and Structural Materials	10
a. Irradiation of US and UC-US Fuels	10
b. Irradiation of Paste Fuels	10
c. Hydrogen in Irradiated Pressure-Vessel Steel	10
12. Mechanism-Related Studies Applied to Sodium Corrosion	11
a. Corrosion Mechanisms in Refractory-Metal/Liquid-Metal Systems	11
b. Distribution Coefficient of Oxygen in Ta-O-Na System and Kinetics of Oxygen Solution in Tantalum	11
c. Polarization Studies in Liquid-Metal Environment	11
13. Internal-Friction Techniques for Analysis of Oxygen in Sodium	11
14. Lithium-Corrosion Studies at Elevated Temperatures	11
15. Development of Techniques of Fabrication and Testing	11
a. Fabrication of Tungsten and Tungsten-Alloy Tubing	11
b. Dimensional and Microstructural Changes during Tube Sinking	12
c. Determination of Elastic Moduli of High-Temperature Materials by Ultrasonics	12
d. Ultrasonic Instrument and Transducer Development	12
e. Development of a Neutron-Image Intensification System	12
f. Infrared Systems for Nondestructive Testing	12
g. Measurement of Thermal Conductivity of Irradiated Fuel as a Function of Burnup and Temperature	12
16. Development of Techniques and Equipment for Alpha-Gamma Hot Cell	13
B. Fast-Reactor Fuel-Element Development and Fabrication	14
1. Metal-Fuel Development	14
a. Development of U-Pu-Zr Alloy Fuel Pins	14
b. Fabrication of U-Pu-Zr Test Fuel Elements	14
c. Phase Compositions in U-Pu-Ti System	17
d. Solid-State Reactions in U-Pu-Zr System	18
e. Heat Content and Heat Capacity of U-15w/oPu-10w/oZr and U-15w/oPu-6w/oTi Alloys	21
f. Compatibility of U-Pu-Zr and U-Pu-Ti Alloys with Potential Jacket Materials	22
g. Fuel-Performance Studies of Uranium-Plutonium Alloys	23
h. Irradiation Behavior of Uranium-Plutonium Alloys	24
2. Oxide-Fuel Development	33
a. Particle-Size Reduction—Design, Construction, and Operation of a Jaw Crusher	33
b. Fabrication of (U,Pu)O ₂ Fuel Bodies for Fast-Reactor Irradiation Studies	35
c. Fuel-Performance Studies of Uranium-Plutonium Oxides	39
3. Carbide-Fuel Development	39
a. Fabrication of (U,Pu)C from Mixed-Carbide Powders Derived from the Metal Alloy by a Hydride-Cycle/Hydrocarbon Route	39
b. Metal Additions to Hyperstoichiometric (U,Pu)C	41
c. Preparation of (U,15w/oPu)C for Vibratorily-Compacted Fuel	45
d. Synthesis of Uranium-Plutonium Monocarbide Solid Solution by Reaction Sintering	45

e. Studies of Rate of Entry in Vibratory Compaction	45
f. Development of Process Equipment for Ceramic Fuels	47
g. Compatibility of Stoichiometric and Hyperstoichiometric Carbides with Potential Jacket Materials	50
h. Fuel-Performance Studies of Uranium-Plutonium Carbides	51
1. Irradiation Behavior of Vibratorily-Compacted UC-20w/oPuC Powders	55
4. Development of Doppler-Element Loading Techniques	60
5. Fast-Reactor Jacket Development	62
a. Improvements in Consolidation and Fabrication of V-15w/oTi-7.5w/oCr	62
b. Alloy Development (Vanadium-Base Alloys)	63
c. Corrosion of Jacket Materials for Sodium-Cooled Reactors	65
d. Development of Refractory-Metal Alloys for Service in Oxygen-Contaminated Sodium	68
e. Exposure of V-20w/oTi Creep Specimens to Sodium	74
f. Uniaxial and Biaxial Creep of V-20w/oTi Exposed to Sodium	75
g. Effect on Biaxial Creep of Exposure of Type 304 Stainless Steel and Nb-1w/oZr Tubing to Sodium	76
h. Linear Thermal Expansion of Vanadium, Titanium, Chromium, and Some Vanadium-Base Binary and Ternary Alloys	77
i. Effect of Heat Treatment on the Uniaxial Creep Strength of Vanadium-Base Alloys	78
j. Uniaxial Tensile Properties of V-15w/oTi-7.5w/oCr at Constant Strain Rate	79
k. Stress and Temperature Dependence of the Activation Energy for the Creep of V-15w/oTi-7.5w/oCr	80
l. Irradiation of Fast-Reactor Jacket Materials	81
6. Zero-Power Fuels and Fuel Elements	84
a. Development of Zero-Power Plutonium Reactor Fuel	84
b. Fabrication of Zero-Power Reactor Fuel from Plutonium Derived from Highly Irradiated Fuel	86
c. Properties of Zero-Power Uranium-Plutonium Metal Fuels	92
d. Flux Perturbation Elements	92
7. EBR-II Assistance	94
a. Soret Effect in the Bismuth-Tin Eutectic Alloy	94
b. Irradiation-Induced Changes in Mechanical Properties of EBR-II Fuel Jackets	97
c. Anomalous Swelling of Mark IA Fuel	102
C. Nuclear Safety	114
1. Radiation Measurements and Personnel Exposures Encountered during Fabrication of Reactivity-Coefficient Specimens	114
2. Penetration of Jacket Materials by Molten U-Pu-Zr and U-Pu-Ti Alloys	115
D. Development of Ceramic Fuels	120
1. Thermal Stability of Plutonium Ceramics	120
a. Gd ₂ O ₃ Evaporation Experiments	120
b. PuO ₂ and (U,Pu)O ₂ Experiments	120
2. Uranium-Mixed Anion Systems	122
a. The U-S-O System	122
b. Synthesis and Properties of Uranium Monoarsenide	123
c. The System UAs-UP	124
d. The System UAs-US	124
e. Phase Studies in the Pseudobinary System UN-UP	124
3. Electrical Properties and Electronic Configurations of the Actinide Metal Compounds with Nonmetals of Groups IV-VI	126
a. Introduction	126
b. Electrical Properties	126
c. Electron Configuration	128
4. Thermal Conductivity and Heat Capacity of Actinide Compounds	130
5. (Th U-Pu) Phosphide Bodies	133
6. Mechanical Properties of Uranium Compounds	135
E. Development of Thorium-Uranium and Thorium-Uranium-Plutonium Fuels	138
1. Introduction	138
2. Thorium-Plutonium Phase Studies	138

3. Thorium-Uranium-Plutonium Phase Studies .	139
4. Thermal Conductivity and Thermal Cycling of Th-U-Pu Alloys .	142
5. Irradiation of Th-U and Th-U-Pu Fuels	143
F. Experimental Irradiations of Fuels and Structural Materials	144
1. Irradiation of Uranium Sulfide	144
2. Irradiation of Paste Fuels	144
3. Hydrogen in Irradiated Pressure-Vessel Steel	147
G. Development of Corrosion-Resistant Jacket and Structural Materials	150
1. Mechanism-Related Studies Applied to Corrosion in Sodium	150
a. Corrosion Mechanisms in Refractory-Metal/Liquid-Metal Systems	150
b. Calculations to Determine the Distribution Coefficient of Oxygen in Ta-O-Na and Nb-O-Na Systems and the Kinetics of Oxygen Solution in Tantalum	152
c. Polarization Studies in Liquid-Metal Environment	156
2. Internal-Friction Techniques for Analysis of Oxygen in Sodium	165
3. Lithium-Corrosion Studies at Elevated Temperatures	168
a. Introduction	168
b. Influence of Silicon on the Lithium Corrosion of Tantalum at 1200°C	169
c. The Influence of Other Additions on the Lithium Corrosion of Tantalum at 1200°C.	169
H. Development of Techniques of Fabrication and Testing	173
1. Fabrication of Tungsten and Tungsten-Alloy Tubing	173
a. Purpose and Scope of Program	173
b. Primary Fabrication	173
c. Secondary Fabrication	174
d. Fabricability Evaluation of 3M-Produced Tubing	175
e. Future Course of Work	176
2. Dimensional and Microstructural Changes during Tube Sinking	176
a. Experimental and Theoretical Status	176
b. Dimensional and Microstructural Changes	176
3. Nondestructive Testing	182
a. Determination of Elastic Moduli of High-Temperature Materials by Ultrasonics	182
b. Ultrasonic Instrument and Transducer Development	183
c. Development of a Neutron-Image Intensification System	184
d. Infrared Systems for Nondestructive Testing	188
e. Measurement of Thermal Conductivity of Irradiated Fuel as a Function of Burnup and Temperature	190
4. Development of Techniques and Equipment for Alpha-Gamma Hot Cell	190
a. Development of Metallographic Techniques for Irradiated Plutonium Fuels	190
b. Autoradiography	192
c. Replication for Electron Microscopy	192
d. Gamma-Activity Profiles of Irradiated Fuel Elements	197

PART II BASIC METALLURGY

A. Metallurgy of the Actinide Metals	201
1. Uranium.	201
a. Crystal Structure of Alpha Phase	201
b. Low-Temperature Transformations—Elastic-Constant Studies	201
c. Irradiation Growth	206
d. The Single Crystal Susceptibility of Alpha from 2°K to 300°K	210
e. Equiatomic Ternary Compounds of Uranium-Aluminum with Group-VIII Transition Elements	211
2. Plutonium	211
a. Preparation of High-Purity Metal	212
b. Electronic Structure of the Alpha Phase	212

c. Effects of Pressure on Transformations.....	215
d. Deformation Mechanisms of Alpha Plutonium.....	217
e. Antemorphic Effects.....	218
3. Neptunium.....	218
a. Electronic Structure.....	218
b. Mössbauer Studies.....	219
B. Actinide Ceramic Compounds.....	220
1. Antiferromagnetism of Uranium Monophosphide.....	220
2. Defect Equilibria in PuO_{2-x}	220
3. Thermodynamic Properties of Plutonium Carbides.....	221
4. Neutron Diffraction Study of Neptunium Dioxide.....	222
5. Magnetic Susceptibilities of Actinide Carbides and Oxides.....	225
C. Deformation and Plasticity.....	227
1. Fatigue Properties of Single Crystals and Polycrystals.....	227
2. Statistical Theory of Flow Stress and Work-Hardening.....	229
3. The Importance of Twinning for the Ductility of CPH Polycrystals.....	231
4. Habit Plane of the Hydride in Zirconium.....	234
5. Hydrogen Embrittlement of Vanadium and Niobium.....	234
D. Transformations.....	238
1. Role of the Structure of Dislocations in the $\text{hcp} \rightarrow \text{bcc}$ Diffusionless Transformation.....	238
2. Effects of Magnetic Transitions on Elastic Properties.....	241
E. Diffusion in Metals.....	246
1. Isotope Effect Studies.....	246
2. Impurity Diffusion in Aluminum.....	249
3. Diffusion in Grain Boundaries.....	250
F. Transition Metals and Alloys.....	251
1. Magnetic Properties.....	251
a. Magnetic Moments in Iron and Nickel Alloys.....	251
b. Magnetic Susceptibilities of Pt- and Pd-base Alloys.....	253
2. Structures and Correlative Scheme of Occurrence of Intermediate Phases.....	254
3. Thermodynamic Properties.....	257
a. Low-Temperature Specific Heats.....	257
b. Thermodynamic Properties of Pd-Cd, Pd-In, Pd-Sn, and Pd-Sb Alloys.....	259
c. The Heats of Formation of Pt-Cu Alloys.....	262
4. Nuclear Magnetic Resonance Studies.....	262
a. Intermetallic Compounds of Aluminum with Group-VIII Transition Elements.....	262
b. Vanadium-Iron Alloys.....	264
c. β -Manganese.....	264
G. Theoretical Studies of Dilute Alloys.....	265
1. Knight Shift in Dilute Silver Alloys.....	265
2. A New Scheme for the Construction of Phase Shifts with Application to NMR.....	266
H. Physical Ceramics Research.....	268
1. Chemical Potentials and Sintering of Pure Metals and Impure Ionic Compounds.....	268
2. Transport Processes in Ionic Oxides.....	268
3. Grain-Boundary Energies of Oxides.....	270
4. Defect Equilibria in Nonstoichiometric Oxides.....	272
5. Statistical Model of Partially Ordered Defects in MO_{2-x}	275
6. Oxygen Diffusion.....	276
a. Application of Proton Activation Analysis.....	276
b. Near-Stoichiometric $\alpha\text{-Nb}_2\text{O}_5$	276
c. Cobalt Monoxide.....	278
7. Interface Migration in Alkali Halides.....	279

I. X-ray and Neutron Diffraction Studies	280
1. Diffraction Instrumentation	280
2. Design of Neutron Instruments for AARR	281
3. Crystallographic Computer Programs . .	281
4. Thermal Neutron Scattering Amplitudes of Ni ⁶¹ and Ni ⁶⁴	282
5. Structure Determination of Manganese Silicide	283
6. Neutron Diffraction Study of Uranyl Nitrate Dihydrate	285
7. Crystal Structure of Selenious Acid	286
8. Crystal Structure of Thorium Nitrate Pentahydrate	287
9. Neutron Diffraction Study of Potassium Ferrocyanide Trideuterate (KFCT)	288
10. Structure and Correlation in Liquid Alloys	289
J. Irradiation Effects and Defects in Metals .	290
1. Migration and Coalescence of Gas Bubbles in Solids	290
2. Irradiation-Induced Defect Clusters in Copper and Gold. Electron Microscopy	290
3. Low-Temperature Charged-Particle Irradiations of Thin Films	291
4. Recovery of Lattice Parameter and Electrical Resistivity in Low-Temperature Neutron-Irradiated Copper.	294
5. Low-Temperature Energy Release in Irradiated Copper .	295
6. Energies and Atomic Configurations of Defects in fcc Metals	297
7. Lattice Dynamics of fcc Crystals with a Morse Potential	299
8. Effect of Low-Temperature Irradiation on Precipitation in Al-Zn Alloys	300
9. Irradiation and Solution Hardening	303
10. Irradiation Hardening	305
K. Corrosion Research	309
1. Low-Pressure Oxidation and Growth Morphology	309
2. Mechanism of Zirconium Oxidation	311
3. Polarization Studies	316
4. Mechanism of Aqueous Corrosion of 1100 Aluminum	319
5. High-Temperature Corrosion of Aluminum Alloys	320
Appendix	322
Publications, Reports, and Patents	322

Part I

Engineering Metallurgy

A. SUMMARY OF ENGINEERING METALLURGY

1. Fast-Reactor Metal-Fuel Development and Fabrication

a. DEVELOPMENT OF U-Pu-Zr ALLOY FUEL PINS

Uranium-plutonium-zirconium alloys are candidate fast-reactor fuels. Double and triple melting were used to dissolve 10w/o and 15w/oZr in uranium and plutonium at a temperature of 1400°C. Single-step alloying required a temperature in excess of 1650°C to dissolve the zirconium, which floated on top of the melt. Crucible erosion was excessive above 1500°C.

The U-15w/oPu-10w/oZr alloy was cast at 1450° to 1500°C into Vycor molds at 200° to 450°C with reasonably good results. A slight warpage occurred at the bottom of the molds. The U-15w/oPu-15w/oZr had to be cast at 1500° to 1550°C. The Vycor showed considerable softening at this temperature, so that the bottom two to three inches of the casting was unsatisfactory. Quartz molds corrected this condition, but they are costly. Carbon molds were also tried but require further development of a mold wash.

b. FABRICATION OF U-Pu-Zr TEST FUEL ELEMENTS

Seventeen EBR-II irradiation test rods were injection cast by the technique described above. The castings were quite brittle. Shearing was not a successful method and the rods were machined to length by means of a lathe. The rods were loaded into stainless steel, V-20w/oTi and Hastelloy jackets by contamination-preventive techniques. Tube-supported restrainers were used in these fuel elements in place of the standard EBR-II stem-type restrainers. Low-frequency jolt bonding was used to sodium bond the rods. Encircling-coil and point-probe pulsed-eddy-current methods were used and compared for determination of bond voids in these elements.

c. PHASE COMPOSITIONS IN U-Pu-Ti SYSTEM

In the U-Pu-Ti ternary system, solidus isotherms have been drawn for alloys in the uranium corner of the system. Differential thermal analysis measurements have established that plutonium stabilizes the high-temperature gamma phase and reduces the equilibrium temperature for the formation of the hexagonal (U,Pu)₂Ti compound.

d. SOLID-STATE REACTIONS IN U-Pu-Zr SYSTEM

Solid-state reaction temperatures have been established in the uranium corner of the U-Pu-Zr system

and solid-state reactions, which occur over a wide range of compositions in the uranium corner, have been analyzed. In addition observations have been noted on the effect of oxygen as a quaternary component and its effect on the structure of U-Pu-Zr alloys.

e. HEAT CONTENT AND HEAT CAPACITY OF U-15w/oPu-10w/oZr AND U-15w/oPu-6w/oTi ALLOYS

H_T-T_{25C} for U-15w/oPu-10w/oZr at 1150°C is 55 cal/g and for U-15w/oPu-6w/oTi is 65 cal/g. The heats of solid-state transformation are 8 cal/g (between 600° and 700°C) and 28.7 cal/g (between 530° and 850°C), respectively. In the titanium-bearing alloy much of the enthalpy increase is due to the heat of formation of U₂Ti.

f. COMPATIBILITY OF U-Pu-Zr AND U-Pu-Ti ALLOYS WITH POTENTIAL JACKET MATERIALS

No liquid-phase formation occurs in diffusion layers in couples of U-Pu-Zr alloys with Type 304 stainless steel of commercial purity at temperatures up to 800°C, and interdiffusion is limited, a year's penetration into stainless steel being only 13μ or less at 700°C. U-Zr alloys with stainless steel form liquid phases at 850°C but not at 825°C. Oxygen diffusing from the steel into either fuel alloy stabilizes the phases in it. At least 50 wt. ppm of oxygen in the steel is required. Vanadium-20w/o titanium is less compatible with U-Pu-Zr alloy than is stainless steel, but the compatibility is improved by replacing some of the titanium in the vanadium alloy with chromium. Replacing the zirconium in the ternary fuel alloy with titanium reduces the compatibility of the alloy with stainless steel, but may slightly improve the alloy's compatibility with V-Ti and V-Ti-Cr alloys.

g. FUEL-PERFORMANCE STUDIES OF URANIUM-PLUTONIUM ALLOYS

Significant advances were made in studies of metallic fuels. Most obvious was the successful achievement of 12.5 and 10.7a/o burnup, respectively, in U-Pu-Zr and U-Pu-Ti alloy specimens. These are the highest known burnups in any metallic plutonium fuel, and may represent the highest burnup in any metallic fuel achieved to date. Less spectacular, but of great importance for the LMFBR program, was the first successful demonstration of the in-reactor compatibility of U-Pu-Zr fuels in iron- and nickel-base

alloy jackets to burnups of 2.4a/o. Fission-gas-release results obtained during the year support the theory that metal fuels will release significant amounts of fission gas after volume increases of approximately 30%.

h. IRRADIATION BEHAVIOR OF URANIUM-PLUTONIUM ALLOYS

A group of 16 U-Pu-Zr alloy fuel rods jacketed in stainless steel, Hastelloy-X, and Hastelloy-X-280 were

removed from EBR-II after burnups up to 5.1a/o at linear heat ratings near 10 kw/ft. Neutron radiography showed that all rods were intact. Fourteen of the elements were removed from their capsules for direct examination. None of the rods showed significant dimensional or other external changes. The successful demonstration of high burnup in U-Pu-Zr fuel rods jacketed in stainless steel has led to considerable interest in this fuel system as advanced driver fuel for EBR-II.

2. Fast-Reactor Oxide-Fuel Development and Fabrication

a. COMMINATION AND VIBRATORY LOADING OF (U,Pu)O₂ FOR IRRADIATION

A miniature jaw crusher with micrometer adjustments was designed and used to prepare angular particulate feeds for vibratory compaction. A group of 24 experimental oxide-loaded rod-type fuel elements were fabricated by vibratory techniques for EBR-II irradiations.

b. FUEL-PERFORMANCE STUDIES OF URANIUM-PLUTONIUM OXIDES

Two mixed-oxide elements prepared from Dynapak material that had been vibratorily compacted in stainless steel tubes were returned from EBR-II after burnups up to 2.9a/o at linear heat ratings up to 17 kw/ft. Neutron radiography indicated that both rods are intact, and that axial (central) voids had developed throughout most of the length of both fuel rods.

3. Fast-Reactor Carbide-Fuel Development

a. FABRICATION OF MIXED-CARBIDE POWDERS DERIVED FROM THE METAL ALLOY

Characterization and fabrication studies were made on mixed uranium-plutonium carbides produced by a fluidized bed technique as well as by arc-melting and reaction sintering. The powders produced by the fluidized bed technique were found to have a tap density of 4.5 g/cc and a typical sieve analysis of 20.5% +200 mesh, 26.1% -200 +325 mesh and 53.4% -325 mesh.* The powder was moderately sinterable. Typical pellets pressed to green densities of 7.8 to 8.3 g/cc and sintered in an argon atmosphere at 1550° to 1900°C were found to have densities in the range of 90 to 92% of theoretical.

b. METAL ADDITIONS TO HYPERSTOICHIOMETRIC (U,Pu)C

In an effort to reduce the sesquicarbide phase in the hyperstoichiometric mixed carbide, additions of Cr, Mo

and W metals were made to carbide powders produced by arc-melting. Dense two-phase compacts were obtained at 1900°C when either Mo or W was used as the additive. The Cr addition produced a second phase at 1700°C which contained zones of variable uranium and chromium contents. No evidence of (U,Pu)₂C₃ or (U,Pu)C₂ was found in any of the samples, and only small amounts of the additive were found in the (U,Pu)C matrix.

c. PREPARATION OF (U, 15w/oPu)C FOR VIBRATORILY-COMPACTED FUEL

Arc-melting of a uranium-plutonium alloy with carbon was used to form buttons of mixed carbides. These buttons were crushed to pass a 325 mesh screen and the powder produced was compacted and sintered.

d. SYNTHESIS OF URANIUM-PLUTONIUM MONOCARBIDE SOLID SOLUTION BY REACTION SINTERING

Studies were made on the synthesis of (U,Pu)C solid solutions by reaction sintering of mixtures of

* U. S. Standard Sieve

uranium dicarbide, uranium hydride and plutonium hydride.

e. STUDIES OF RATE OF ENTRY IN VIBRATORY COMPACTION

Study and application of vibratory compaction for loading particulate fuels into jackets was continued in 1966. Infiltration rates of smaller particles into beds of coarse particles was studied. A gamma-ray absorptometer was designed and constructed to evaluate the filling density of columnar fuel rods.

f. DEVELOPMENT OF PROCESS EQUIPMENT FOR CERAMIC FUELS

Two new glovebox lines were installed during 1966. One of these contains a high-purity argon atmosphere and equipment for carbide pellet fabrication. The second contains a tungsten-element furnace and plasma-process equipment. The induction plasma torch and power source is scheduled for early 1967 delivery.

g. COMPATIBILITY OF STOICHIOMETRIC AND HYPERSTOICHIOMETRIC CARBIDES WITH POTENTIAL JACKET MATERIALS

The interactions of a number of iron-, nickel-, and vanadium-base alloys with (U,Pu)C were studied over the temperature range of 700° to 900°C. The jacket materials were tested for 1000 hours with single-phase (U,Pu)C and with hyperstoichiometric carbide (5.25w/o equivalent carbon). Two alloys, Haynes 56

and V-15w/oCr-5w/oTi, were found to have no reaction with either carbide composition after 1000 hours at 800°C.

h. FUEL-PERFORMANCE STUDIES OF URANIUM-PLUTONIUM CARBIDES

Three rod-type elements containing vibratorily-compacted physically-mixed UC and PuC powders, vibratorily-compacted (U,Pu)C powder, and pellets of (U,Pu)C, respectively, were returned from EBR-II after irradiation to burnups up to 3.1a/o, at linear heat ratings up to 26 kw/ft. Neutron radiography indicated that all rods are intact.

i. IRRADIATION BEHAVIOR OF VIBRATORILY-COMPACTED UC-20w/oPuC POWDERS

Considerable progress was made in 1966 in relating microstructural aspects of irradiated mixed UC and PuC powders to in-reactor behavior. Detailed optical metallography and electron microscopy were performed on several mixed-carbide specimens irradiated in MTR and described in the 1965 Annual Report. The PuC phase in the higher-burnup specimens was found to have swelled into the original distributed void spaces between the carbide particles. The fission-gas bubbles in PuC_{1-x} were generally larger and more interconnected than those in the PuC_{1+x} . This accounts for the greater fission gas release noted in the UC-Pu C_{1-x} specimens. The PuC_{1+x} contained as yet unidentified small second-phase particles.

4. Development of Doppler-Element Loading Techniques

The vibratory loading technique was applied to the manufacture of doppler test elements. Previous doppler elements were loaded with pellets made of UO_2 and PuO_2 granules stuck together with a silica glass. In use the fuel column was held rigidly against thermal

expansion by pistons in the ends of the elements. Once the pellet element was cycled, it could not be used again. Elements filled by vibratory compaction can be shaken up and returned to the original fuel dimensions by recompaction.

5. Fast-Reactor Jacket Development

a. IMPROVEMENTS IN CONSOLIDATION AND FABRICATION OF V-15w/oTi-7.5w/oCr

The V-15w/oTi-7.5w/oCr alloy is amenable to conventional consolidation and fabrication methods and little difficulty in commercial processing of the alloy is expected.

Consolidation by double arc-melting with consumable electrodes under an inert atmosphere makes control of chromium contents possible in finished ingots. The V-15w/oTi-7.5w/oCr alloy is adaptable to primary fabrication by double extrusion and is easily tube-reduced—based on studies carried out at ANL on a three roll tube-reducer. The alloy should be

amenable to reduction on commercial two-roll (Rock-rite) devices. With proper lubrication the alloy can be mandrel and/or plug drawn through conventional carbide drawing dies.

A comprehensive evaluation of the properties of this alloy is now under way at ANL and elsewhere.

b. ALLOY DEVELOPMENT (VANADIUM-BASE ALLOYS)

Progress is being made in the initial scaleup in the production and fabrication of both the V-10w/oCr and the V-15w/oCr-5w/oTi alloys. Consolidation has followed conventional patterns and secondary fabrication operations are being studied.

The V-Cr and V-Cr-Ti alloys seem responsive to thermal treatments and an optimum treatment (thermal and/or mechanical) is probably the key to both improved creep properties and practical fabrication. A continuing effort will be directed toward obtaining useful knowledge concerning the identity and morphology of the microstructural constituents of both of these alloys.

While it is intended that some finished product from the initial scaleup of both alloys be made available for further testing, determination of optimum processing parameters is of equal importance. These parameters, along with property data, can provide the required "feed-back" that should be factored into any larger-scale processing of either alloy.

c. CORROSION OF FUEL-JACKET MATERIALS FOR SODIUM-COOLED REACTORS

V-20w/oTi has been exposed to flowing (2.45 cm/sec) sodium containing 1 to 6 wt. ppm oxygen in the temperature range 550° to 750°C for periods up to 475 hours. Under these conditions the alloy gains weight according to a parabolic rate law. The weight gains are the result of solution of oxygen in the metal, resulting in a hardened layer at the surface. The rate constant determined from two or more runs at a given temperature varied from 2.7×10^{-4} (mg/cm²)² hr⁻¹ at 550°C to 30×10^{-4} (mg/cm²)² hr⁻¹ at 750°C.

d. DEVELOPMENT OF REFRACTORY-METAL ALLOYS FOR SERVICE IN OXYGEN-CONTAMINATED SODIUM

In flowing (6.1 m/sec) sodium at 650°C, containing oxygen at concentrations maintainable by cold-trapping, vanadium-base alloys gain weight at a low rate (less than that predicted by parabolic kinetics). V-20w/oTi has received the longest exposure (~175 days) but unalloyed vanadium, V-15w/oTi-7.5w/oCr, and V-5w/oCr all show lower weight gains than V-20w/oTi under the low (<10 wt. ppm) oxygen conditions.

At oxygen concentrations greater than 10 wt. ppm, vanadium and vanadium-base alloys lose weight. Under such conditions, titanium and chromium are beneficial alloying elements.

e. EXPOSURE OF V-20w/oTi CREEP SPECIMENS TO SODIUM

Exposure of V-20w/oTi to sodium at 650°C containing ~20 wt. ppm oxygen results in serious degradation of creep properties, even allowing for reduction in load-bearing area. Short-time (seven day) exposure to sodium at 650°C containing <10 ppm oxygen does not result in degradation of creep properties. Studies are being made under conditions in which the corrosion process is solution of oxygen.

f. UNIAXIAL AND BIAXIAL CREEP OF V-20w/oTi AFTER EXPOSURE TO SODIUM

Exposure of V-20w/oTi to high-oxygen sodium (20 wt. ppm O₂) at 650°C decreases its creep strength, rupture life, and ductility in uniaxial and biaxial creep tests conducted at 650°C and 15 to 30 kg-mm⁻² stress. The degrading effect on material properties is greater when the alloy is under load during sodium exposure. A less pronounced decrease in these properties results from exposure to low-oxygen sodium (10 ppm O₂).

g. EFFECT ON BIAXIAL CREEP OF EXPOSING TYPE 304 STAINLESS STEEL AND Nb-1w/oZr TO SODIUM

Exposure of Type 304 stainless steel to low-oxygen sodium (10 wt. ppm O₂) at 650°C results in an increase in rupture life and ductility, and a slight decrease in creep strength for biaxial creep tests conducted at 550°C and 25 to 28 kg-mm⁻² stress.

Nb-1w/oZr is severely embrittled when exposed to high-oxygen sodium (20 wt. ppm O₂) under load at 650°C. In biaxial creep tests at 700°C and 30 kg-mm⁻² stress the rupture life is less than two hours and the rupture ductility is of the order of 0.1 percent.

h. LINEAR THERMAL EXPANSION OF VANADIUM, TITANIUM, CHROMIUM, AND SOME VANADIUM-BASE BINARY AND TERNARY ALLOYS

The thermal-expansion characteristics of vanadium, titanium, chromium and some vanadium-base alloy were determined for the temperature range 0°C to 1000°C. Mean expansion coefficients based on least-square fitted polynomials are tabulated.

i. EFFECT OF HEAT TREATMENT ON THE UNIAXIAL CREEP OF VANADIUM ALLOYS

The V-Ti and V-Ti-Cr alloys can be heat treated to improve their creep strength, rupture life and rupture ductility. The optimizing heat treatment for V-20w/oTi is one hour at 1000°C, while the optimizing heat treatment for V-15w/oTi-7.5w/oCr and V-5w/oTi-15w/oCr is one hour at 1250°C. The resulting grain size in all three alloys is between 0.03 and 0.05 mm.

j. UNIAXIAL TENSILE PROPERTIES OF V-15w/oTi-7.5w/oCr at CONSTANT STRAIN RATE

Uniaxial tensile properties for 1250°C annealed V-15w/oTi-7.5w/oCr were determined between 25°C and 800°C for a constant strain rate of 2×10^{-4} sec⁻¹. The ultimate tensile strength and yield stress (0.2 percent offset) increase slightly between 200°C and 400°C as a result of strain aging, but otherwise decrease gradually with increasing temperature. Total

elongation increases from 29 to 50 percent while the uniform elongation decreases from 18 to 7 percent over the test-temperature range.

k. STRESS AND TEMPERATURE DEPENDENCE OF THE ACTIVATION ENERGY FOR THE CREEP OF V-15w/oTi-7.5w/oCr

The activation energy for the creep of V-15w/oTi-7.5w/oCr is independent of stress and temperature for the range 15 to 60 kg mm⁻² stress and 500° to 850°C temperature. The experimental value is 89,000 cal mole⁻¹. Impurities make a stress-sensitive contribution to the creep strength.

l. IRRADIATION OF FAST-REACTOR JACKET MATERIALS

Numerous structural materials specimens were placed in EBR-II for irradiations at 500° to 670°C to exposures from 6×10^{21} to 1×10^{23} n/cm². Emphasis is on vanadium alloys. The first irradiated specimens are expected early in 1967.

6. Zero-Power Fuels and Fuel Elements

a. DEVELOPMENT OF ZERO-POWER PLUTONIUM REACTOR FUEL

The development of design, manufacturing processes, and specifications for ZPPR fuel elements have been completed, and the specifications have been proved practical through pilot-lot manufacture of 73 of the elements.

b. FABRICATION OF ZERO-POWER REACTOR FUEL FROM PLUTONIUM DERIVED FROM HIGHLY IRRADIATED FUEL

The development of zero-power reactor fuel and experimental-physics elements were a significant effort. A pilot ZPPR fuel element fabrication was carried out to test the validity of the procurement specifications for ZPPR fuel. About 20 kg of ²³w/o²⁴⁰Pu was fabricated into 212 fuel elements for test of the neutronic effects of ²⁴⁰Pu and ²⁴¹Pu. The alloy used for these elements was Pu-1.2w/oAl. The alloy was cast as billets that were rolled to 0.089-inch-thick strip. Core plates were blanked and coined from the strip. The core plates were cleaned, inspected and loaded into stainless steel jackets. Personnel exposure was limited in the operations requiring glove manipulation of the

alloy to keep from exceeding allowable gamma radiation and neutron dosages.

c. PROPERTIES OF ZERO-POWER URANIUM-PLUTONIUM METAL FUELS

Air-corrosion tests started in 1964 and 1965 and terminated in 1966 led to the selection of U-20w/oPu-2.5w/oMo as the most corrosion-resistant of a range of U-Pu-Ti, U-Pu-Zr, and U-Pu-Mo compositions considered for SEFOR fast critical experiments. Tests on similar alloys with the plutonium content increased to 25w/o and 30w/o showed that the resistance to air corrosion was improved by a carbon content of 1500 to 2300 wt. ppm. A 50% reduction in section by rolling a casting of U-25w/oPu-2.5w/oMo at 650°C results in brittleness but does not affect isotropy of thermal expansion.

d. FLUX PERTURBATION ELEMENTS

A number of flux-perturbation specimens were prepared. These consisted of cylindrical and annular (napkin ring) plutonium bodies in stainless steel jackets. The annular specimens were of three thicknesses.

7. EBR-II Assistance

a. SORET EFFECT IN THE BISMUTH-TIN EUTECTIC ALLOY

One of the major causes of EBR-II seal-plug rotation difficulties is considered to be formation and growth of a solid bismuth phase in the lower temperature regions of the seal. Experiments designed to study such segregation (Soret effect) in the tin-bismuth system have demonstrated that growth of a bismuth phase under conditions of seal operation is possible. Experiments are now under way to define the magnitude of the phenomenon in quantitative terms.

b. IRRADIATION-INDUCED CHANGES IN THE MECHANICAL PROPERTIES OF EBR-II FUEL JACKETS

Burst tests of the EBR-II fuel jackets show that up to 400°C, the burst strength of the irradiated jackets is approximately 30,000 psi higher than for unirradiated material. Ductility loss in the irradiated jackets is extensive. At 400° to 450°C, the original 10% elongation is reduced by displacement damage to values near 0.5%. A ductility minimum also appears at temperatures above 800°C, and is attributed to effects of helium from (n,α) reactions.

c. ANOMALOUS SWELLING OF MARK IA FUEL

In EBR-II Mark I fuel elements the actual plenum gas pressure during operation is approximately

$$P_g = \frac{32.981}{10.019 - y} \text{ kg/cm}^2;$$

but to provide for a mild power excursion, equivalent to a 100°C rise in the temperatures of all the components, the equation becomes

$$P_g = \frac{36.716}{8.862 - y} \text{ kg/cm}^2,$$

where y is the percent of fuel-swelling. The resulting hoop stress in the jacket is calculated by use of the

thick-wall tube formula. Actually, some second-order effects result in lesser pressures than these equations give, but omission of these effects from design calculations serves to minimize the consequences of the inadvertent presence of an occasional bad-acting fuel pin. Fuel swelling has been estimated from nondestructive measurement of changes in sodium level. Despite a scatter in data, the swelling appears to be proportional to the square of the burnup. The plenum/sodium volume ratio is such that the gas pressure would near infinity long before the pin could swell 16.8%, the swelling required for the fuel to fill the annulus.

Mark IA fuel elements have enough additional plenum space (on account of shorter, though more enriched, pins) to allow almost twice as much fuel-swelling, yet any improvement they offer is slight. The swelling behavior differs from one pin to the next, and the controlling parameters are not as yet determined. There is some evidence that impurities present in reprocessed pins and scrap may be beneficial, but the limiting gas pressure is still reached before mechanical restraints can play a role.

Reductions in the mass of the restrainer and in the amount of sodium above the fuel pin are features of Mark IB design that provide so much more room in the plenum for gas that mechanical restraint can eventually control. When this restraint is radial,

$$y = 16.84\% \quad \text{and} \quad P = \frac{506.9 \cdot \text{BU}}{6.736 - \text{BU}};$$

and when axial restraint is controlling

$$y = 20.30 \quad \text{and} \quad P = \frac{506.9 \cdot \text{BU}}{8.120 - \text{BU}}.$$

Since the fission-gas bubble pressure for fixed swelling depends on the surface tension and mechanical strength of the fuel as well as on the plenum-gas pressure, the hoop stresses set up when swelling is arrested can be calculated. During free swelling the fission-gas bubble pressure actually decreases with burnup.

8. Nuclear Safety

a. RADIATION MEASUREMENTS AND PERSONNEL EXPOSURES ENCOUNTERED DURING FABRICATION OF REACTIVITY-COEFFICIENT SPECIMENS

Radiation measurements, dose-rate computations

and the study of personnel radiation exposures during the fabrication of high-burnup plutonium (containing less than 80% Pu²³⁹) have been made, and the information derived has been applied to the establishing of radiation-protection requirements for future work with recycled plutonium.

b. PENETRATION OF TYPE 304 STAINLESS STEEL AND V-20w/oTi BY MOLTEN U-Pu-Zr AND U-Pu-Ti ALLOYS

The rate of penetration of V-20w/oTi by U-15w/oPu-10w/oZr and by V-15w/oPu-6.5w/oTi is about 0.09 ± 0.005 mm/sec at 1300°C, accelerating to 0.22 ± 0.013 mm/sec at 1400°C, but corresponding data for penetration of Type 304 stainless steel show wide

scatter. Metallographic and microprobe studies indicate penetration of both jacket alloys to occur by dissolution attack around subgrains, by diffusion through a liquid viscous layer and in the solid state, and by convection. The rate of penetration of the stainless steel by U-15w/oPu increases from 0.02 mm/sec at 1180°C to 0.25 mm/sec at 1400°C. Carbon in the melt inhibits penetration of the stainless steel by uranium at temperatures above 1300°C.

9. Development of Ceramic Fuels

a. THERMAL STABILITY OF PLUTONIUM CERAMICS

Langmuir and Knudsen evaporation experiments were made on gadolinium sesquioxide in the temperature range from 2140° to 2600°K. Two sets of data obtained with Knudsen cells yielded an average value of $\Delta H_o^\circ = 464.0 \pm 1.0$ kcal per mole for the assumed evaporation reaction

Pellets of PuO₂ and 80w/oUO₂-20w/oPuO₂ were fabricated and attempts were made to determine their oxygen-to-metal ratios. The plutonia appeared to react with alumina, tungsten, molybdenum, and rhenium, but not with platinum and iridium under various test conditions. Preliminary evaporation experiments on PuO₂ indicate that the evaporation rate becomes approximately linear with time at 2000°K.

b. URANIUM-MIXED ANION SYSTEMS

The portion of the system bounded by uranium, UO₂ and US₂ has been under investigation. Melting points and electrical resistivity were determined for the compounds (US, U₂S₃, U₃S₅, US₂, UOS, and UO₂) found in this area. Oxidation characteristics of the three US₂ polymorphs were found to be similar to those of US. Uranium dioxide showed an extensive range of solid solubility in UOS.

The preparation and some properties of uranium monoarsenide are described. It has the NaCl-type structure common to many other actinide compounds, has a melting point of 2450°C, and preferentially loses arsenic at elevated temperatures. The compound exhibits greater volatility at high temperatures than either UP or US. UAs shows complete mutual solid solubility with UP and US, whereas no solid solution was observed in the systems UAs-UC and UAs-UN.

Samples were prepared at different compositions in the pseudobinary system UN-UP and were melted

under helium, pressurized nitrogen and helium-nitrogen mixtures. The tentative phase diagram shows no intermediate compound formation and only 1% solubility of UN in the UP lattice. A eutectic occurred at about 2300°C and 40w/oUP.

c. ELECTRICAL PROPERTIES AND ELECTRONIC CONFIGURATIONS OF THE ACTINIDE METAL COMPOUNDS WITH NONMETALS OF GROUPS IV TO VI

The electrical properties of the actinide compounds with anions of Groups IV to VI, all of which compounds have the NaCl-type crystal structure, have been studied in an attempt to understand conduction processes in these potential fuel materials for fast reactors. Electronic configurations of the actinide compounds were also investigated by comparison of their unit cell volumes and metal radii with those of corresponding rare earth compounds. Effective valences obtained from these data were used to show that systematic changes in the transport properties can be correlated with the electronic configurations of the actinide compounds. Electrical conduction appears to be governed by a systematic change of carrier concentration in the $s + d$ valence band and scattering caused by $s + d, f$ transitions. A separation of the f states is apparently responsible for the semiconductor properties of PuS.

d. THERMAL CONDUCTIVITY AND HEAT CAPACITY OF ACTINIDE COMPOUNDS

The heat capacity and thermal conductivity of UC, UP and US were determined between room temperature and 650°C by a transient technique with a laser as a heat pulse source. It was found that the lattice resistance to the flow of heat in this group of compounds is essentially temperature independent and that the temperature variation of the thermal conductivity can be attributed to the electronic contribution. Thermal diffusivity measurements on UO₂ have been

made in a tantalum furnace between 300° and 1500°C with a lead sulfide photoelectric temperature detector. Calculated thermal conductivity values are in good agreement with literature values.

e. (Th-U-Pu) PHOSPHIDE BODIES

Studies have been conducted of the high-temperature compatibility of UP with the following refractory metals: Ti, Zr, Nb, Mo, Ta, and W. Titanium and zirconium exhibited significant reaction with UP at 1600°C, niobium at 1800°C, and molybdenum at 2000°C. The composition UP-Ta melted at 2200°C while tungsten did not react with UP at this temperature.

X-ray diffraction revealed that there was a difference in vaporization behavior between UP pellets and powder. Uranium monophosphide powder showed es-

entially congruent vaporization but phosphorus was selectively lost from the UP pellets.

f. MECHANICAL PROPERTIES OF URANIUM COMPOUNDS

Strength and deformation tests were carried out on sintered uranium dioxide at temperatures up to 1900°C in vacuo. There was little difference in the maximum fiber stress in the bars at the slow, medium or fast strain rates. There was essentially no deformation in any of the specimens until test temperatures were above 1250°C.

The maximum fiber stress recorded occurred under a medium strain rate (263 g/sec), which yielded a modulus of rupture of 1915 kg/cm². Marked changes in deformation behavior were observed in the brittle-to-ductile transition region around 1250°C.

10. Development of Thorium-Uranium and Thorium-Uranium-Plutonium Fuels

a. PHASE STUDIES

In order to improve our understanding of the properties and irradiation behavior of ternary U-Pu-base metal alloys, phase studies are in progress in the system Th-U-Pu, as well as in the U-Pu-Ti and U-Pu-Zr systems. In the Th-Pu binary system, X-ray diffraction was used to establish the solubility limit of plutonium in alpha thorium at 700° and 900°C. In the Th-U-Pu system reactions involving the liquid phase were analyzed over the range of temperatures of interest for fuel alloy development. In addition to phase studies in the Th-U-Pu system, thermal conductivity

between 100°C and 800°C and thermal cycling behavior of two ternary alloys (Th-10U-10Pu and Th-20U-10Pu) have been measured.

b. IRRADIATION BEHAVIOR

Two Th-20w/oU fuel pins, two Th-10w/oU-10w/oPu pins, and two of Th-20w/oU-10w/oPu, all jacketed in V-20w/oTi have been irradiated in CP-5 at maximum jacket temperatures of 590°C to a maximum of 15.8a/o (U + Pu) burnup. Neutron radiographs at 13.3a/o burnup showed zero elongation of the Th-U pins, but 8% elongation for the Th-U-Pu pins.

11. Experimental Irradiation of Fuels and Structural Materials

a. IRRADIATION OF US AND UC-US FUELS

Irradiation continued on US specimens in the MTR. Preparations are being made to irradiate UC-US pellets in CP-5.

b. IRRADIATION OF PASTE FUELS

Irradiation of a paste fuel element was undertaken at the request of the Fuels and Materials Branch. Initial examination of the element by neutron radiog-

raphy disclosed that the element failed by cladding rupture.

c. HYDROGEN IN IRRADIATED PRESSURE-VESSEL STEEL

An investigation was made to determine if the pressure-vessel steel 212-B when irradiated was susceptible to hydrogen embrittlement. Two different hydrogen contents were studied, both in unirradiated and in irradiated material. The conclusion discredited the possibility of a catastrophic hydrogen-induced brittle failure in a 212-B reactor vessel.

12. Mechanism-Related Studies Applied to Sodium Corrosion

a. CORROSION MECHANISMS IN REFRACTORY-METAL/LIQUID-METAL SYSTEMS

Study of the tantalum-tin system has been completed. The success of the rotating disc technique has been demonstrated. Of particular importance is the application of the technique to distinguish between reaction types in a heterogeneous reaction and to identify the controlling reaction as a function of system variables.

Application of fundamental thermodynamics and kinetics concepts to refractory metal-alkali metal systems provides a powerful tool for understanding the experimental behavior of these systems and for determining fruitful areas of investigation and operation. This is demonstrated in some detail for the Nb-O-Na system.

b. DISTRIBUTION COEFFICIENT OF OXYGEN IN Ta-O-Na SYSTEM AND KINETICS OF OXYGEN SOLUTION IN TANTALUM

Equilibration of body-centered cubic refractory metals with sodium of low interstitial impurity concentration, followed by analysis of the refractory metal through application of internal friction techniques, offers great promise of satisfactory interstitial analysis of sodium at very low levels of interstitial concentration. The technique has been demonstrated for the Ta-O-Na system.

c. POLARIZATION STUDIES IN LIQUID-METAL ENVIRONMENT

Experimental difficulties in maintaining a suitably insulated electrode have resulted in temporary suspension of this program. The data obtained to date appear to demonstrate that it is possible to obtain polarization curves in high-temperature sodium systems and that the thickness of corrosion film may be reduced by externally applied polarization current.

13. Internal-Friction Techniques for Analysis of Oxygen in Sodium

Measurements of internal friction in refractory-metal wires that have been equilibrated with sodium are potentially an extremely sensitive technique for determining less than 1 wt. ppm of oxygen, and probably of nitrogen and carbon, in sodium. Tantalum ap-

pears to be the most appropriate refractory metal. The measured height of the internal friction peaks can be calibrated with the concentration of the impurity, and the peak temperature for a given frequency identifies the impurity.

14. Lithium-Corrosion Studies at Elevated Temperatures

Above 1000°C, tantalum suffers severe localized (intergranular corrosion and cracking) attack in lithium. However, solution of a small percentage of silicon in the lithium effectively inhibits attack up to at least

1200°C. The silicon appears to function by forming a tantalum-silicon compound, relatively inert to lithium, at the tantalum surface.

15. Development of Techniques of Fabrication and Testing

FABRICATION OF TUNGSTEN AND TUNGSTEN-ALLOY TUBING

Notable progress has been made at ANL in the fabrication of high-quality tungsten-alloy tubing.

Tube-reduction operations have shown promise as an economical method of conditioning as-extruded tube-blank surfaces. Such operations can materially improve the chances for survival of the product in sub-

sequent processing. After modifications for warm working, the ANL three-roll tube-reducer may enable tube-reduction to be used as a fabricating process in place of some of the more conventional drawing operations.

Point-swaging has been improved to the extent that point failures in tube drawing are now seldom experienced. This success combined with the use of improved lubricants has permitted heavier drafts and eliminated many annealing operations. New core-removal techniques have been tested and found to be both useful and time saving, but still costly.

Tungsten-alloy tubing produced by 3M using powder extrusion and sintering has been found to be equally as fabricable as more conventional starting materials, as shown by redraw tests conducted at ANL.

All of the above gains are being factored into a revised and, it is hoped, much less expensive technology of tubing fabrication for the tungsten and tungsten alloys.

b. DIMENSIONAL AND MICROSTRUCTURAL CHANGES DURING TUBE SINKING

The dimensional changes occurring during the tube sinking of six metals are being measured as part of a program for acquiring data useful in the prediction of deformation behavior during the sinking process. The metals tested are aluminum, α -brass, nickel, Monel metal, mild steel, and Type 304 stainless steel. Parameters measured are: γ_0 , the ratio of the wall thickness before sinking, t_0 , to the corresponding outer radius, r_0 , of the tube; $\epsilon\lambda = \ln(l/l_0)$, the true elongation strain, l_0 and l being respective lengths after zero or j reduction passes; $\epsilon_\theta = \ln(F_0/F_j)$, the true hoop strain, the bar representing the mean tube radii after zero or j reduction passes; $\ln(t_0/t_j)$, the thickness strain, which is represented by the difference between the $\epsilon\lambda$ and ϵ_θ curves, and profiles of microhardness and grain shape (as determined by lineal intercept analysis) across the tube wall.

c. DETERMINATION OF ELASTIC MODULI OF HIGH-TEMPERATURE MATERIALS BY ULTRASONICS

A new vacuum furnace for ultrasonic measurements at high temperature has been placed in operation. The furnace can operate at temperature $>2500^\circ\text{C}$. The temperature gradient problem across the test sample has been much reduced with the use of this new equipment. Measurements on rods of Type 304 stainless steel indicate that ultrasound echo patterns and sound attenuation characteristics vary from sample to sample. The "trailing pulses" generated by mode conversion in the index region of a rod of V-15w/oTi-7.5w/oCr are significantly higher than in the case of V-20w/oTi.

Increasing the annealing temperature of the ternary alloy from 700°C to 1500°C , increases Young's modulus by about 6.5% and the shear modulus by about 7.9%, but reduces Poisson's ratio by about 4%.

d. ULTRASONIC INSTRUMENT AND TRANSDUCER DEVELOPMENT

Porous nickel backings for lead zirconate-titanate ultrasonic transducers have been successfully fabricated. The use of these backings in ultrasonic probes provides good results for ultrasonic nondestructive test frequencies of 5 Mc and higher. At lower frequencies, the trailing pulses are not sufficiently attenuated in the conical rear-faced backing material. Experience with the porous metal material indicates that a porous tungsten backing would contribute to improved low-frequency results. Work on this material is under way.

e. DEVELOPMENT OF A NEUTRON-IMAGE INTENSIFICATION SYSTEM

A new 15 cm diameter target neutron-image intensifier tube has provided a light yield $5\times$ better than that of the first intensifier tube, and $2\times$ better relative neutron-gamma response. These improvements are attributed, at least partially, to an improved spectral match between the photoemissive layer and the light emitted from the neutron scintillator, and to decreased gamma absorption in the neutron scintillator layer. The improved light output of the intensifier tube has permitted direct visual observation of gross thermal neutron images for incident thermal neutron intensities as low as $50\text{ n/cm}^2\text{-sec}$ and television observation of such images for thermal neutron intensities as low as $2 \times 10^4\text{ n/cm}^2\text{-sec}$ for a vidicon television system and $200\text{ n/cm}^2\text{-sec}$ for a more sensitive image orthicon television system.

f. INFRARED SYSTEMS FOR NONDESTRUCTIVE TESTING

Employment of a cooled detector in a radiometer has provided the capability for fast, sensitive infrared detection of unbonded areas. Several reactor-component objects for inspection have been tested by infrared and other nondestructive test systems, and a comparison between the test results was made. The speed of the technique and the fact that its use does not require physical contact with the test sample offer the infrared test method some advantages.

g. MEASUREMENT OF THERMAL CONDUCTIVITY OF IRRADIATED FUEL AS A FUNCTION OF BURNUP AND TEMPERATURE

The thermal-pulse method for measuring thermal conductivity and thermal diffusivity has been applied

at room temperature to irradiated U-5w/oFs fuel alloy material at three different burnup levels. A significant decrease in thermal conductivity has been observed for samples at burnup levels of 1.8a/o and 3.0a/o. Measurements on these materials at temperatures up to 600°C are planned. Elevated-temperature measure-

ments on a UO_2 -SS₃₄₇ unirradiated cermet fuel material (to 800°C) were made as an aid in checking out the vacuum furnace before cave installation. The thermal-conductivity measurements on a cermet fuel showed the poor thermal properties of a stringered fuel sample.

16. Development of Techniques and Equipment for Alpha-Gamma Hot Cell

Much progress was made during the year in increasing the capability of the Metallurgy Alpha-Gamma Hot Cell. The principal addition was a shielded metallograph. Other developments include alpha and

beta-gamma autoradiography, improved replication techniques for electron microscopy, and techniques for obtaining gamma-activity profiles by using scintillation spectrometry.

B. FAST-REACTOR FUEL-ELEMENT DEVELOPMENT AND FABRICATION

1. Metal-Fuel Development

a. DEVELOPMENT OF U-Pu-Zr ALLOY FUEL PINS (H. F. JELINEK AND D. A. KRAFT)

A development program is under way to fabricate U-Pu-Zr fuel pins and assemble them into fuel elements. The program involves developing methods of fabrication and assembly for large numbers of fuel rods, and the fabrication and assembly of a small number of test specimens for immediate use on a best-effort basis. The suitability of U-Pu-Zr alloys for remote fabrication by injection casting also is considered.

(1) Alloy Preparation

The first attempts to prepare U-Pu-Zr alloy by melting the elemental metals together showed the difficulty of this method. The wide difference of melting temperature, vapor pressure and density of the three metals and the reactivity of the alloy with crucible materials required the development of a step-wise alloying technique to prepare the irradiation test elements. This technique is not recommended for quantity alloy production. Coreduction or arc melting of a U-Zr master alloy may be required preliminary to injection casting in production scale.

A U-15w/oPu-10w/oZr alloy was the first alloy fabricated for test specimens. Alloying was done in a lime-stabilized, zirconia crucible. An alloying temperature of 1650°C–1700°C was required to dissolve all the zirconium. At this temperature the metal reacted with the crucible. The oxygen analysis of the alloy was 1800 ppm.

The alloy was next prepared in a series of melts to lower the alloying temperature. Two binary alloys, U-6w/oZr and Pu-12w/oZr were made in yttria-coated, graphite crucibles and poured into graphite molds also coated with an yttria wash. The melt charges were heated to 1400°C and held for 50 to 60 minutes. The resulting binary alloys appeared to be satisfactorily homogeneous. The oxygen content was between 500 and 1,000 ppm.

The same method was also used to prepare ternary U-15w/oPu-15w/oZr alloys. However, the results were not as good. The additional zirconium in the binary alloys would not dissolve completely at 1400°C and above 1400°C the crucible was attacked. Thoria and yttria washes on zirconia crucibles did not provide sufficient protection to keep the oxygen content below 1,000 ppm.

A hydrogen-reduced zirconia crucible was tried next.

The crucible was prepared by firing the crucible in a hydrogen atmosphere at 1800°C to 1850°C for four hours to make an oxygen-deficient ZrO₂ surface, which was expected to be more nearly inert to molten zirconium. The preliminary results indicate that it may resist attack by the alloy better than the untreated crucibles. Further studies are being made with partly reduced crucibles and with zirconium-zirconia crucibles.

(2) Injection Casting

Injection casting of the U-15w/oPu-10w/oZr alloy was done in precision Vycor molds. Melting was in yttria coated, graphite crucibles. The molds (0.130-in., 0.148-in., and 0.165-in. I.D. by 18-in. long) were coated with yttria in the usual manner. Casting temperatures of 1450°C to 1500°C were required. The molds were preheated to temperatures of 200°C to 450°C from top to bottom, respectively.

Some warpage at the bottom of the molds showed that the Vycor was beginning to soften. However, no melting was observed and analysis did not indicate a significant silicon contamination. The casting surfaces were smooth, but were more sensitive to mold coating defects than hitherto.

Some injection-casting melts of the U-15w/oPu-15w/oZr alloy also have been made. The increased zirconium content raises the temperature necessary to cast the alloy to the range of 1500°C to 1550°C. Increased mold temperatures of 300°C to 600°C were required. The Vycor molds deformed at the bottom and decreased the usable pin length by 2 to 3 inches.

Quartz and carbon molds have been tested. The quartz molds which soften at 1600°C have produced castings with no warpage. The quartz molds cost about \$9 each, or five times the cost of Vycor molds. Further development of protective coating materials for the carbon mold is required. Yttria-coating on carbon molds, does not appear to be adequate for the U-Pu-Zr alloys.

b. FABRICATION OF U-Pu-Zr TEST FUEL ELEMENTS (H. F. JELINEK AND A. G. HINS)

A group of seventeen fuel elements were fabricated and assembled for irradiation tests in EBR-II. The fuel pins were U-15w/oPu-10w/oZr alloy, 0.144-in. diameter by 13.5-in. long. The pins were jacketed in stainless steel and vanadium-alloy tubes of the dimensions shown by Table 1. The fuel elements have tube-

TABLE 1. LOADING DATA

Rod Number	Fuel Pin ^(a)		Jacket Tube			
	Number	Alloy (<i>w/o</i>)	Length (in.)	Alloy	O.D. (in.)	Wall (in.)
BA01	R358-1	U-15.0Pu-10.3Zr	32.32	304SS	0.198	0.015
BA02	R358-2	U-15.0Pu-10.3Zr	32.32	304SS	0.198	0.015
BA03	R363-1	U-15.2Pu-10.0Zr	32.32	304SS	0.198	0.015
BA04	R372-3	U-15.2Pu-9.9Zr	32.32	304SS	0.198	0.015
BA05	R372-4	U-15.2Pu-9.9Zr	32.32	304SS	0.198	0.015
BB01	R372-5	U-15.2Pu-9.9Zr	29.11	304SS	0.208	0.020
BC01	R372-6	U-15.2Pu-9.9Zr	32.32	316SS	0.198	0.015
BC02	R358-3	U-15.0Pu-10.3Zr	32.32	316SS	0.198	0.015
BC03	R358-4	U-15.0Pu-10.3Zr	32.32	316SS	0.198	0.015
BD01	R358-5	U-15.0Pu-10.3Zr	24.00	V-20T ₁	0.198	0.015
BD02	R358-6	U-15.0Pu-10.3Zr	24.00	V-20T ₁	0.198	0.015
BD03	R358-7	U-15.0Pu-10.3Zr	24.00	V-20T ₁	0.198	0.015
BD04	R358-8	U-15.0Pu-10.3Zr	24.00	V-20T ₁	0.198	0.015
BD05	R363-2	U-15.2Pu-10.0Zr	24.00	V-20T ₁	0.198	0.015
BE01	R358-9	U-15.0Pu-10.3Zr	22.05	V-20T ₁	0.198	0.015
BE02	R358-10	U-15.0Pu-10.3Zr	22.05	V-20T ₁	0.198	0.015
BE03	R363-3	U-15.2Pu-10.0Zr	22.05	V-20T ₁	0.198	0.015

^(a) All fuel pins were 0.144-in. diameter by 13.50-in. long.

supported restrainers that are held in place by two circumferential beads in the jacket.

(3) Fuel Fabrication

The U-Pu-Zr was alloyed and cast in three steps. Two binary alloys of U-6*w/o*Zr and Pu-12*w/o*Zr were made to dissolve the zirconium. Magnesium crucibles with yttria coatings were used. The melts were heated to 1400°C and held for 50 to 60 minutes. The alloys were poured from the crucible into plate-type molds.

The two alloys were combined in the injection casting melt with additional zirconium to adjust the composition to 10*w/o* zirconium. Casting temperatures of 1450°C to 1500°C were required to successfully cast into the 0.148-in. diameter Vycor molds. A maximum of 12 molds could be used per melt.

The castings were hard and brittle. The usual method of shearing the castings to correct length was not successful. The castings had to be machined to length in a lathe at 400 to 500 RPM with a carbide tool. Some edge chipping occurred during machining.

Density measurements were found to be useful for estimating composition of the alloy. The U-15*w/o*Pu-10*w/o*Zr fuel pins have a density of 15.8 gm/cc compared to 14.8 gm/cc for the U-15*w/o*Pu-14*w/o*Zr.

(4) Fuel Element Assembly

The fuel pins were loaded and bonded by means of modified EBR-II techniques. Most modifications were necessitated by the use of tube-supported restrainers.

A variety of restrainers have been incorporated in experimental and production fuel elements for the purpose

of keeping the fuel submerged in the sodium. Figure 1 shows representative types of restrainers that have been tested. Type (a) is the EBR-II design with a 0.08-in. diameter stem and 0.140-in. diameter bottom pad. The stem occupies a significant part of the expansion space. Type (b) was an attempt to reduce the loss of expansion space by substituting a 0.040-in. diameter wire for the stem and pad of the EBR-II restrainer. Test fuel elements of this design were made. Type (c) was an early design of a collapsible restrainer made of slotted, thin-wall tubing with a bottom pad. Several variations of this were made, all of which caused difficulty in bonding and sodium level detection.

The stem or tubular restrainers occupy valuable void space and are not an effective design for a fuel element having a long expansion space above the sodium. Tube supported restrainers have been developed for these as shown in Figure 1, Types (d, e, and f). Type (d) is held in position by indentations staked into triple grooves in the restrainer body. Type (e) is held in place by a bead that is rolled into the tube immediately above and below the restrainer plug. Peripheral channels or axial holes are provided for sodium flow. In gas-bonded oxide and carbide fuel elements a porous metal plug, type (f), is employed to keep the fuel in position.

The condition that the fuel body should be allowed to expand without restraint has resulted in the design of various spring-type restrainers. One of these is shown in Figure 1 (g).

The seventeen elements have the type (e) restrainer also shown in Figure 2. A tubing cutter modified with a blunt disc and nylon rolls was used to roll the beads

FIG. 1. Production and Experimental Restrainers for EBR-II Elements.

into the jackets. A shoulder on the disc prevented grooving the jackets more than 0.005-in. deep. Metallography, tube burst tests, and compression tests on sample specimens have indicated that the beads actually strengthen the tubing at the restrainer position.

The following sequence of loading was used: Circumferential beads were rolled into the jacket at the bottom of the restrainer position before the tubes were put into the loading hood. After loading the sodium and fuel pin into jacket, the assemblies were heated to 150°C and gently vibrated at 60 Hz to melt the sodium and settle the fuel pin. The ¼-in. long restrainers were loaded into each jacket and allowed to settle against the bead. The elements were cooled and the second bead was rolled into the jacket above the restrainer on each element. The end plugs were welded into the jackets by standard TIG welding techniques. The V-20w/oTi was welded in a double-shielded chamber to prevent weld oxidation. The elements were decontaminated, removed from the hood, and leak tested.

The assembled elements were soaked at 500°C for two hours and impact bonded 2,000 times. An extension on the bonder was required for the 22-in. to 33-in. long rods. The elements were sealed into the chamber under an inert atmosphere of 6 psig to prevent oxidation of the vanadium alloy jackets. A summary of the loading data is given in Table 1.

Fuel-element sodium-column height was determined by X-radiography. Column heights ranged from 0.13-in. to 0.44-in. above the fuel pin at room temperature. Their average was 0.30-in. and was slightly below the specified mean height of 0.35-in.

The annular sodium bond was inspected at 150°C by eddy-current techniques. A pulsed, differential, encircling coil was used. This eliminated spurious results from shrinkage voids that are generally present in

solidified sodium. Bond-test results were difficult to analyze. The greater thickness of the jacket wall (0.015-in.) and the sodium annulus (0.011-in.) reduced the ability of the test equipment to differentiate between bond defects and less harmful tube wall thickness variation. Sensitivity was improved through the use of a masked aperture point-probe coil. A standard fuel rod with a 1/16-in. diameter bond defect was used to calibrate the test equipment.

Two fuel rods had to be rebonded. Two fuel rods were dejacketed and their bonds were visually inspected. Visual observations correlated well with the eddy-current test traces. In the end, fifteen fuel rods were prepared for secondary encapsulation. They contained no bond defects larger than the ¼₁₆-in. x ¾₁₆-in. maximum defect specified for EBR-II.

c. PHASE COMPOSITIONS IN U-Pu-Ti SYSTEM (D. R. O'BOYLE AND H. V. RHUDE)

Previous work on the effects of ternary additions on the solidus temperature of uranium-plutonium alloys has shown that either titanium or zirconium is effective in increasing the solidus temperature. Alloys of interest as fast-reactor fuels lie in the uranium corner of the uranium-plutonium-titanium and the uranium-plutonium-zirconium ternary systems and contain 10 to 20w/oPu and 5 to 15w/oTi or Zr. In both systems an increase in either titanium or zirconium (at a constant plutonium content) increases the solidus temperature while an increase in the plutonium content decreases the solidus of the alloy. The properties of ternary alloys of interest as fast-reactor fuels were summarized in the previous annual report.⁽¹⁾ In addition to having a high breeding ratio, high thermal conductivity, and excellent resistance to sodium corrosion, the ternary alloys are compatible with certain potential jacket materials up to 800°C. The uranium-plutonium-zirconium alloys containing at least 10w/oZr are compatible with Type 304 stainless steel to 800°C while the uranium-plutonium-titanium alloys are compatible with the stainless steel to 650°C and vanadium-base jacket alloys to 700°C.

During the past year, work has been directed at establishing the composition of phases that exist in the U-Pu-Ti ternary system and at establishing transformation temperatures of ternary alloys. In addition, the effects of various oxygen levels on the structure of uranium-plutonium-zirconium alloys have been evaluated.

The effect of varying titanium and plutonium content on the solidus temperature of uranium-rich alloys is shown in Figure 3. As in the uranium-titanium binary system, an increase in the titanium content increases

350-938

Fig 2 Jacket Tube Supported Restrainer, Type (c).

⁽¹⁾ Annual Progress Report for 1965, Metallurgy Division, ANL-7155, 14-25.

FIG. 3. U-Pu-Ti Solidus Isotherms.

106-8885

FIG. 4. Effect of Plutonium on the Transformation of Gamma to the $(U,Pu)_2Ti$ Ternary Intermediate Phase.

the solidus temperature whereas in the uranium-plutonium binary system the solidus is decreased by an increase in plutonium content. The solidus temperatures, established by differential thermal analysis (DTA), were determined for specimens prepared from high-

purity uranium and plutonium and crystal-bar titanium.

For all alloys in the uranium corner of the uranium-plutonium-titanium system, the body-centered cubic gamma solid solution is stable below the solidus temperature. In the binary uranium-titanium system, gamma decomposes to the hexagonal U_2Ti intermediate phase at $899^\circ C$ as shown in Figure 4. These data on the solid-state transformation temperatures were obtained at various heating and cooling rates from $0.25^\circ C$ per minute to $5^\circ C$ per minute. An increase in plutonium content to $16.7 a/o$, stabilizes the gamma phase down to $817^\circ C$. A further increase in plutonium content to $23.3 a/o$ stabilizes the gamma to $782^\circ C$ as shown in the figure. At more rapid heating and cooling rates, the transformation temperature indicated on heating is only slightly affected by the increased heating rate whereas the transformation temperature indicated on cooling is reduced. Generally, it was observed that the transformation from gamma to $(U,Pu)_2Ti$ occurs rapidly so that the gamma phase cannot be retained by quenching.

In order to establish the equilibrium phase relations in the uranium corner of the uranium-plutonium-titanium system, six different alloys were homogenized and isothermally annealed at temperatures between $810^\circ C$ and $565^\circ C$. These alloys were examined metallographically and the composition of the phases determined by electron microprobe analysis. A typical isothermal section through the ternary system at $750^\circ C$ is shown in Figure 5. In the three alloys shown, the $(U,Pu)_2Ti$ compound is the matrix phase and the gamma solid solution appears dark. As shown in the micrograph at $4000\times$ the gamma solid solution has decomposed on quenching from $750^\circ C$ to form phases that are stable at lower temperatures. It appears that the $(U,Pu)_2Ti$ compound extends into the ternary system to about $13 a/o Pu$ at $750^\circ C$ and has a narrow range of solid solubility for titanium. At lower temperatures, the gamma phase field recedes rapidly toward the plutonium corner of the ternary system. Hence, the plutonium content in the gamma phase of two-phase $\gamma + (U,Pu)_2Ti$ alloys may vary considerably depending on the alloy's location in the two-phase field. The maximum solubility of plutonium in the $(U,Pu)_2Ti$ compound appears to be $18 a/o$ at $565^\circ C$.

d. SOLID-STATE REACTIONS IN U-Pu-Zr SYSTEM (D. R. O'BOYLE AND H. V. RHUDE)

An analysis of the solid-state reactions in the uranium corner of the uranium-plutonium-zirconium system is given in Figure 6. This analysis is based on the established reactions that occur in the limiting binary

REDUCED 30% IN REPRODUCTION

FIG. 5. U-Pu-Ti Isothermal Section at 750°C Schematic.

106-8886

FIG. 6. Solid State Reactions in the Uranium Corner of the U-Pu-Zr System.

systems and on ternary solid state transformations as established by dilatometry. A eutectoid reaction is indicated as Class I and a peritectoid reaction is indicated by Class III following the notation of Rhines.⁽²⁾ The Class II isothermal reactions that occur at 655°C and

⁽²⁾ Rhines, F. N., *Phase Diagrams in Metallurgy*, McGraw-Hill, New York (1956).

at 600°C occur over a wide range of compositions in the uranium corner of the system. Hence, all alloy compositions of interest as fast-reactor fuels undergo a specific volume change at 600°C and at 655°C. At temperature below 600°C, the α -uranium + ζ (U,Pu) + δ UZr₂ three phase region is stable to room temperature.

Ternary alloys prepared from reactor-grade uranium

and plutonium may contain as much as 1200 wt. ppm oxygen, which has a strong influence on the cast structure of the alloy. In the uranium-plutonium-zirconium system, it has been established that α -zirconium is stabilized by oxygen and appears as zirconium-rich particles in the matrix, whereas in the uranium-plutonium-titanium ternary system, α -titanium is stabilized by oxygen. In order to quantitatively establish the effect of oxygen on the structure of uranium-plutonium-zirconium alloys, a series of alloys was prepared having a constant ratio of plutonium to uranium of 1:4 and with a controlled oxygen content between 100 and 1200 ppm. In alloys containing 22a/o and 30a/oZr with 16a/o and 14a/oPu, respectively, it has been found that the volume fraction of α -zirconium varies linearly with oxygen content. At 1000 ppm oxygen, the volume fraction of α -zirconium is approximately 5 v/o.

e. HEAT CONTENT AND HEAT CAPACITY OF U-15w/oPu-10w/oZr AND U-15w/oPu-6w/oTi ALLOYS (H. SAVAGE)

The heat contents of U-15w/oPu-10w/oZr and U-15w/oPu-6w/oTi were measured in a drop calorimeter.

FIG. 7. Heat Content Above 25°C of U-15w/oPu-10w/oZr Alloy.

TABLE 2. THERMAL PROPERTIES OF U-15w/oPu-10w/oZr

Temperature (°C)		$H_T - H_{25}$ (cal/g)		C_p (cal/g/°C)
		Calc.	Obs.	Calc.
25		-0.1		0.031
100		2.4		0.034
200		5.9		0.037
300		9.8		0.040
400	306.5	13.9	10.2	0.043
500	402.4	18.5	14.1	0.047
	505.3		18.7	
	599.6		23.9	
600		23.3		0.050
650		32.6		0.038
700	696.1	34.7	34.7	0.040
800	798.1	38.7	38.9	0.043
900	897.0	43.2	43.3	0.046
1000	997.0	47.9	47.4	0.049
1100	1097.0	53.0	52.4	0.052
1150	1140.3	55.6	55.1	0.054

The heat content of U-15w/oPu-10w/oZr alloy increases monotonically to 55 cal/g at 1150°C as shown in Figure 7. There is an abrupt increase between 600 and 700°C because of the occurrence of phase transformations in that temperature interval. The values of heat content for the alloy are about 2 cal/g higher, on the average, than those of unalloyed uranium.⁽³⁾ The heats of transformation of the alloy and of uranium are nearly equal, 8 cal/g for the alloy compared to 7.9 cal/g for the uranium solid-state transformations.

The values of the heat content and the specific heat are shown in Table 2 and, along with their temperature ranges of application, are expressed as follows:

$$\begin{aligned}
 H_T - H_{25^\circ\text{C}} &= 0.9 + 0.0310T + 0.0000155T^2 \text{ cal/g} \\
 &\quad (25-600^\circ\text{C}) \\
 &= 14.2 + 0.0185T + 0.0000152T^2 \text{ cal/g} \\
 &\quad (650-1150^\circ\text{C}) \\
 C_p &= 0.0310 + 0.000310T \text{ cal/g/}^\circ\text{C} \quad (25-600^\circ\text{C}) \\
 &= 0.0185 + 0.000304T \text{ cal/g/}^\circ\text{C} \quad (650-1150^\circ\text{C})
 \end{aligned}$$

The standard deviations between the observed and calculated heat-content values are 0.35 and 0.26 for

⁽³⁾ Savage, H., and Seibel, R. D., *Heat Capacity Studies of Uranium and Uranium-Fissium Alloys*, ANL-6702 (1963).

FIG. 8. Heat Content of U-15w/oPu-6w/oTi Alloy Above 25°C.

TABLE 3. THERMAL PROPERTIES OF U-15w/oPu-6w/oTi

Temperature (°C)		$H_T - H_{25}$ (cal/g)		C_p (cal/g/°C)
		Calc.	Obs.	Calc.
25		0		0.033
100		2.6		0.0349
200		6.3		0.0374
300		10.1		0.0400
	301.0		10.1	
	399.8		14.4	
400		13.9		0.0425
	499.5		18.6	
500		18.7		0.0450
550		20.9		0.0463
	598.9		24.2	
	696.9		31.3	
	796.8		39.8	
850		49.6		0.0355
	895.5		51.2	
900		51.5		0.0470
	995.2		55.8	
1000		56.1		0.0507
	1095.0		61.4	
1100		61.7		0.0619
1150		64.9		0.0669
	1150.4		65.0	

the lower and upper temperature ranges, respectively.

The heat content of U-15w/oPu-6w/oTi alloy in-

creases monotonically to 65 cal/g at 1150°C as shown in Figure 8. Between 550°C and 850°C the heat released by the three-phase transformations produces a rapid rise in the enthalpy curve about equal to the sum of the $\alpha \rightarrow \beta$, $\beta \rightarrow \gamma$ and $\gamma \rightarrow$ liquid heats of transformation in unalloyed uranium. A large portion of the total rise in the enthalpy curve is due to the heat of formation of the compound, U_2Ti . This raises the heat-content curve for the alloy substantially above that of the unalloyed uranium.

The heat content and specific heat of the U-15w/oPu-6w/oTi alloy are listed in Table 3. The calculated values are based on the following equations:

$$\begin{aligned}
 H_T - H_{25^\circ\text{C}} &= -0.7 + 0.0324T + 0.0000126T^2 \text{ cal/g} \\
 &\quad (25-550^\circ\text{C}) \\
 &= 57.1 - 0.0531T + 0.0000521T^2 \text{ cal/g} \\
 &\quad (850-1150^\circ\text{C}) \\
 C_p &= 0.0324 + 0.0000252T \text{ cal/g/}^\circ\text{C} \quad (25-550^\circ\text{C}) \\
 &= 0.0531 + 0.0001042T \text{ cal/g/}^\circ\text{C} \quad (850-1150^\circ\text{C})
 \end{aligned}$$

The total heat in the transformation region, 550 $\rightarrow$ 850°C is 28.7 cal/g. The standard deviations between the observed and calculated heat-content values are 0.07 and 0.08 for the lower and upper temperature ranges, respectively.

f. COMPATIBILITY OF U-Pu-Zr AND U-Pu-Ti ALLOYS WITH POTENTIAL JACKET MATERIALS (S. T. ZEGLER)

Earlier results⁽⁴⁾ of compatibility tests show that alloys of U-14 to 18w/oPu-10 to 14w/oZr coupled with Type 304 stainless steel at 800°C for 5000 hours do not form any liquid phase in the diffusion layers. An extension of this compatibility work during 1966 resulted in the diffusion-penetration data for 700°C that were used as points in the curves of Figure 9. Extrapolation of the data for penetration into the stainless steel, on the basis of a parabolic rate law, indicates a penetration into the stainless steel of 13 microns or less in one year. Penetration of diffusing elements into the fuel is approximately 40% of that into the steel. A comparison of the 700°C curve for the U-10w/oZr/304SS system with the curve for the U-15w/oPu-10w/oZr/304SS system indicates that a reduction in plutonium content reduces the reaction rate.

Tests of U-10w/oZr/304SS diffusion couples show that liquid phases form in them at 850°C but not at 825°C. The non-occurrence of a liquid phase at the lower temperatures is attributed to the formation of zirconium-rich barrier phases. Those include alpha zirconium, the gamma-2 of the U-Zr system, and the

⁽⁴⁾ ANL Metallurgy Division Annual Progress Report for 1965, p. 23 of ANL-7155.

gamma of the Zr-Ni-O system,⁽⁵⁾ all these stabilized by diffusion of oxygen from commercial stainless steel into the fuel alloy. (Type 304 stainless steel usually contains 200 to 450 wt. ppm of oxygen.) The minimum oxygen content for promoting the stability of high-zirconium phases has not been determined.

Figure 9 also shows that V-20w/oTi and V-15w/oTi-7.5w/oCr are more subject to diffusion penetration when coupled with U-Pu-Zr alloys than is stainless steel. The resistance of the V-Ti-Cr alloy to diffusion penetration by the fuel metals, however, is greater than that of V-20w/oTi. The enhancement of fuel/jacket compatibility by substitution of chromium for some of the titanium in vanadium-base jacket alloys will therefore be studied further.

Type 304 stainless steel and U-15 to 22w/oPu-10 to 12w/oTi alloys rather than U-Pu-Zr fuels, are liable to excessive interaction at temperatures above 650°C. In couples of the stainless steel with the indicated U-Pu-Ti alloys interpenetration is extensive at 750°C, and liquid phases form at temperatures lower than 800°C. The plutonium in the alloy decreases the temperature at which a liquid phase forms. For example, a liquid phase forms in U-22w/oPu-11.8w/oTi at 650°C.

Preliminary tests of couples of U-Pu-Ti alloys with V-20w/oTi or V-15w/oTi-7.5w/oCr show only a slight increase in resistance to interpenetration over that of couples of U-Pu-Zr alloys.

g. FUEL-PERFORMANCE STUDIES OF URANIUM-PLUTONIUM ALLOYS (W. N. BECK, F. L. BROWN, W. F. MURPHY, AND C. C. CROTHERS)

Subassembly XA07, containing sixteen, 34-in. long U-Pu-Zr alloy fuel elements, was recently removed from the reactor and 14 of these elements are presently being examined in the Metallurgy Alpha-Gamma Hot Cell. Table 4 summarizes the irradiation conditions and observations completed to date. These elements are U-15w/oPu-9w/oZr or U-15w/oPu-12w/oZr fuel pins jacketed in Type 304 stainless steel, Type 316 stainless steel, Hastelloy-X, or Hastelloy-X-280. The fuel elements were operated at maximum jacket temperatures of 630°C and had attained estimated burnups in the range of 4.7 to 5.1 a/o.

Neutron radiography of the irradiated capsules indicated that all fuel elements were intact. The capsules were then punctured and the absence of escaping fission gas also indicated that the jackets of the elements were intact. The fuel elements were then removed from their capsules. Dimensional measurements showed no significant changes in diameter as a result of irradiation.

(5) Nevitt, M. V., and Downey, J. W., *The Zirconium-Rich Corners of the Ternary Systems Zr-Co-O and Zr-Ni-O*, Trans. AIME **221**, 1014-1017 (October 1961).

46662

FIG. 9. Cladding Penetration vs. Time at 700°C for U-Pu-Zr Alloys with Type 304 Stainless Steel and V-base Alloys.

tion. Fuel-pin lengths were determined by neutron radiography and disclosed an average increase of 1.9%. The fuel pins were not seated on the bottom closures of the jackets, but were elevated an average of 0.2 in. These elements had been intentionally assembled without axial fuel restrainers to allow possible axial fuel movement.

The as-received capsules, which are 40-in. in length, were noticeably bowed. The average bow was 0.21 in. and could not be correlated to reactor position and amount of bow. Relaxation of residual stresses in the capsule tubing at reactor operating temperatures may have caused the deformation. The fuel elements inside the capsules were also bowed an average of 0.12 in.

The neutron radiographs of the fuel pins within the jackets revealed one to two separations, which varied in width from ~0.020 in. to 0.060 in. The separations were also detected in the gross gamma scan of the fueled portion of the element. A radiograph of element NB-28 and the gamma scan can be seen in Figure 10. A fuel-column separation, which was also noted for this same alloy when irradiated to 12.5 a/o burnup, is described in this report under Section "Irradiation Behavior of Metallic Fuels." Table 4 lists the design parameters, operating conditions, results of a preliminary examination.

The examination of these elements, which is presently in progress, will include density measurement, gamma scan, determination of the level of the sodium bond and fission gas recovery. Following these examinations, the

TABLE 4. IRRADIATION CONDITIONS AND PRELIMINARY RESULTS OF THE U-Pu-Zr FUEL ELEMENTS IN XA07 SUBASSEMBLY

Specimen Number	Design Parameters					Operating Conditions			Preliminary Postirradiation Examination Results				
									Capsule	Element		Fuel rod	
	Fuel composition, w/o	Effective density, %	Cladding alloy	Cladding OD, in.	Clad. thick., in.	Max. kw/ft	Max. clad. temp., °C	Burnup, a/o, U + Pu	Bow, in.	Bow, in.	Length change, in.	Length change, %	Separation of fuel from bottom plug, in.
ND28	U-15Pu-9Zr	73.1	304 SS	0.205	0.019	10.5	630	5.1	0.06	0.03	0.016	0.4	0.12
ND41	U-15Pu-9Zr	73.8	304 SS	0.205	0.019	10.5	625	4.9	0.18	0.06	0.018	0.9	0.18
ND32	U-15Pu-9Zr	73.8	316 SS	0.196	0.015	10.5	605	4.7	0.75	0.14	0.100	1.9	0.18
ND43	U-15Pu-9Zr	74.5	Hast.-X	0.196	0.015	10.5	615	4.9	0.00	0.05	0.037	-0.7	0.31
ND25	U-14Pu-12Zr	73.5	304 SS	0.205	0.019	10.0	600	4.4	0.37	0.10	0.011	4.0	0.12
ND27	U-14Pu-12Zr	73.1	304 SS	0.205	0.019	10.0	605	4.5	0.23	0.14	0.015	2.8	0.18
ND26	U-14Pu-12Zr	73.9	316 SS	0.196	0.015	9.5	590	4.3	0.18	0.12	0.011	5.4	0.12
ND29	U-14Pu-12Zr	72.2	316 SS	0.196	0.015	9.5	595	4.4	0.37	0.19	0.011	6.0	0.12
ND30	U-14Pu-12Zr	72.3	316 SS	0.196	0.015	10.0	615	4.9	0.25	0.14	0.021	1.1	0.25
ND34	U-14Pu-12Zr	72.6	Hast.-X	0.196	0.015	10.0	610	4.7	0.15	0.11	0.041	0.0	0.31
ND35	U-14Pu-12Zr	74.9	Hast.-X	0.197	0.015	10.0	615	4.9	0.00	0.07	0.010	-1.5	0.37
ND37	U-14Pu-12Zr	63.8	Hast.-X-280	0.207	0.015	9.5	610	4.9	0.12	0.26	0.003	2.3	0.12
ND39	U-14Pu-12Zr	65.4	Hast.-X-280	0.207	0.015	9.5	610	4.8	0.12	0.22	0.007	2.3	0.06
ND44	U-14Pu-12Zr	66.4	Hast.-X-280	0.208	0.015	9.5	600	4.7	0.12	0.17	0.004	1.5	0.25

elements will be subjected to a detailed metallographic study.

Four fuel elements continuing under irradiation in EBR-II include two each of U-Pu-Zr and U-Pu-Ti alloys jacketed in V-20w/oTi tubing. These elements are being irradiated at maximum jacket temperature of 540°C and have reached a calculated 5.2 a/o burnup. Additional details on the design of the fuel elements and the irradiation conditions are summarized in Table 5.

A postirradiation examination was conducted on 19 experimental U-Pu-Fs elements irradiated in XA01 subassembly in the EBR-II reactor. The fuel pins in the elements measured 0.144-in. in diameter and were jacketed in 0.009-in. thick Nb-1w/oZr, Hastelloy-X, or Nb-4w/oV alloy. Visual examination of the elements confirmed earlier indications obtained from neutron radiographs of the encapsulated elements that the jackets of those elements had collapsed in the region of gas plenum, above the fuel pin.⁽⁶⁾ The collapse of the jacket presumably occurred when the subassembly was lowered into the hot reactor sodium before the sodium in the irradiation capsules had fully melted, and was the result of the lateral pressure of molten sodium kept from expanding vertically by a plug of sodium that had not yet melted. External dimensional measurements taken on the elements failed to show significant diameter or length changes. The accuracy of these measurements is

confirmed by the fact that the measured volumes were nearly unchanged. Exceptions were the three elements with the collapsed tubing, which showed an average volume decrease of 4%.

The most significant variations noted in the 19 U-Pu-Fs elements were in the lengths of the fuel pins. All fuel pins elongated within their jackets except the three in collapsed jackets. Table 6 summarizes irradiation conditions and fuel-pin length changes for the 19 elements.

Irradiations were concluded on a series of six experimental fuel elements of U-Pu-Fs alloy. The elements were irradiated in gas-annulus temperature-controlled capsules in MTR. Each element consisted of a 13-in. long fuel-pin, 0.144 in. in diameter, sodium-bonded to a jacket with an OD of 0.186 in. and a wall thickness of 0.015 in. The average sodium annulus thickness, before irradiation, was 0.006 in. Table 7 summarizes information on the irradiation conditions for the six elements and the dimensional changes observed.

Postirradiation examination disclosed that two of the experimental elements had jacket failures as a result of excessive fuel swelling. Swelling of the fuel pins in each of the remaining elements was accommodated by the sodium-filled annulus between the fuel pins and the jacket.

h. IRRADIATION BEHAVIOR OF URANIUM-PLUTONIUM ALLOYS (W. N. BECK)

Significant advances were made during 1966 in (1) demonstrating high fuel burnups through improvements

⁽⁶⁾ Reactor Development Program Progress Report, ANL-7255, pp. 25-26 (September 1966).

1-5885

FIG. 10. Neutron Radiograph and Gamma Scan of Element NB-28.

TABLE 5. STATUS OF METAL FUEL IRRADIATIONS IN PROGRESS IN EBR-II REACTOR

Test Reactor	Capsule or S/A No.	Specimen Number	Design Parameters					Operating Conditions			
			Fuel composition, w/o	Effective density, %	Cladding composition, w/o	Cladding OD, in.	Clad. thick., in.	Max. kw/ft	Max. clad. temp., °C	Burnup to date	
										a/o, U + Pu	fiss/cc $\times 10^{-20(a)}$
EBR-II	XG06	ND23	U-15Pu-10Zr	66	V-20Ti	0.209	0.016	9.1	540	5.0	12.1
EBR-II	XG05	ND24	U-15Pu-10Zr	66	V-20Ti	0.209	0.016	9.1	535	4.8	11.6
EBR-II	XG05	NC17	U-15Pu-10Ti	63	V-20Ti	0.209	0.016	9.1	540	4.9	10.9
EBR-II	XG06	NC23	U-15Pu-10Ti	63	V-20Ti	0.209	0.016	9.1	540	5.2	11.5

(a) Based on effective density.

TABLE 6. IRRADIATION CONDITIONS AND FUEL PIN ELONGATION OF U-Pu-Fs AND U-Pu-Fz FUEL ELEMENTS IN XA01 SUBASSEMBLY

Rod No.	Fuel Composition, w/o	Jacket		Max. Fuel Temp., °C	Max. Jacket Temp., °C	a/o Burnup	Fuel Pin Elongation, %
		Composition, w/o	Condition				
C93	U-20Pu-10Fs	Nb-1Zr	Stress relieved	450	435	0.57	2.8
C97	U-20Pu-10Fs	Nb-1Zr	Stress relieved	445	432	0.56	2.1
C98	U-20Pu-10Fs	Nb-1Zr	Stress relieved	445	432	0.55	2.7
C99	U-20Pu-10Fs	Nb-1Zr	Stress relieved	445	432	0.56	2.9
C100	U-20Pu-10Fs	Nb-1Zr	Stress relieved	445	432	0.56	1.8
C101	U-20Pu-10Fs	Nb-1Zr	Stress relieved	450	435	0.56	2.8
CM01	U-20Pu-10Fz	Nb-1Zr	Stress relieved	450	435	0.56	4.7
CA01	U-15Pu-10Fz	Nb-1Zr	Stress relieved	470	445	0.57	3.6
CB02	U-15Pu-10Fz	Nb-1Zr	Stress relieved	465	443	0.58	4.6
CB03	U-15Pu-10Fz	Nb-1Zr	Stress relieved	460	440	0.57	3.9
CB04	U-15Pu-10Fz	Nb-1Zr	Stress relieved	460	440	0.57	4.5
*CD01	U-15Pu-10Fz	Nb-1Zr	Annealed	455	437	0.57	-0.6
*CD02	U-15Pu-10Fz	Nb-1Zr	Annealed	445	432	0.56	-0.43
LA02	U-15Pu-10Fz	Hast.-X	Annealed	450	435	0.56	3.5
PA01	U-15Pu-10Fz	Nb-4V	Annealed	450	435	0.56	3.5
CG02	U-10Pu-10Fz	Nb-1Zr	Stress relieved	465	443	0.58	4.1
CG03	U-10Pu-10Fz	Nb-1Zr	Stress relieved	445	432	0.57	3.7
*CJ01	U-10Pu-10Fz	Nb-1Zr	Annealed	450	435	0.56	-0.4
PB02	U-10Pu-10Fz	Nb-4V	Annealed	455	437	0.57	4.8

* Jacket was collapsed in gas plenum area prior to irradiation by expansion of sodium in irradiation capsule.

TABLE 7. EXPERIMENTAL U-Pu-Fz ALLOY ELEMENTS IRRADIATED IN MTR

Element No.	Fuel Comp., w/o	Jacket Material	Max. Burnup, a/o	Max. Jacket Temp., °C	Volume Increase, %		Max. Dia. Increase, %	Fuel Pin Length Increase, %
					Element	Fuel pin		
CK01	U-10Pu-10Fz	Nb-1w/oZr	2.3	555	(a)	26.4	17.5	2.3
CE03	U-15Pu-10Fz	Nb-1w/oZr	2.3	555	(a)	17.4	26.0	1.6
EC01	U-15Pu-10Fz	Vanadium	2.7	555	1.5	17.5	3.2	1.8
CB01	U-15Pu-10Fz	Nb-1w/oZr	1.3	555	0.3	14.7	—	-4.0
EA01	U-15Pu-10Fz	Vanadium	1.6	555	0.3	13.8	—	-5.4
LA01	U-15Pu-10Fz	Hastelloy-X ^(b)	1.6	555	0.3	13.1	—	1.1

(a) Jacket ruptured—measurement not taken.

(b) Contained tungsten barrier layer.

in materials and design, and (2) achieving a better understanding of factors leading to fission-gas disengagement from metal fuels.

Two specimens in the form of prototype fuel elements, which were recently removed from instrumented capsules in the CP-5 reactor, established new performance levels for metal fuel systems. One specimen was U-18.5w/oPu-14.1w/oZr alloy; the other was U-15w/oPu-10w/oTi alloy. Both were sodium-bonded to V-20w/oTi alloy jacket with effective fuel densities near 68%. Both specimens were in excellent condition and are presently undergoing a detailed postirradiation examination.

The U-Pu-Zr specimen reached an analyzed 12.5 a/o burnup (28×10^{20} fiss/cm³) at a maximum jacket temperature of 655°C. A photograph of the specimen after irradiation is shown in Figure 11. Periodic non-destructive examination of the capsule during irradiation showed that the pin attained a maximum elongation of 3%, and this occurred at 4.2 a/o burnup. The amount of elongation did not change throughout the remainder of the irradiation.

Diametral changes in the jacketed specimen were calculated from volume changes measured by immersion. An average increase in diameter of 0.0002 in. was observed. No measurable increase in length was noted. The jacket was punctured and the recovered fission gas is in the process of being analyzed for fission-product isotopes.

The metallographic examination, which is in progress, shows that there was no significant penetration of the fuel into the jacket. A transverse section of the fuel pin can be seen in Figure 12. The presence of a ring in the fuel is believed to be the boundary of a phase transformation zone that would occur in this alloy at 650°C. Photographs of the fuel-jacket interface as well as typical porosity in the specimen can be seen in Figure 13.

The condition of the fuel, as well as the calculated final operating gas plenum pressures (~2200 psi), indicates that the specimen could have attained still higher burnups without jacket failure.

The U-Pu-Ti specimen reached an analyzed 10.7 a/o burnup (25×10^{20} fiss/cm³) at a maximum jacket

EI-5629

FIG. 11. U-18.5w/oPu-14.1w/oZr Alloy Specimen Jacketed in V-20w/oTi Alloy Tubing after Irradiation to 12.5 a/o Burnup at a Maximum Jacket Temperature of 655°C.

EI-5888

15X

FIG. 12. Transverse Section of U-18.5w/oPu-14.1w/oZr Jacketed in V-20w/oTi Tubing and Irradiated to 12.5 a/o Burnup at a Maximum Jacket Temperature of 655°C.

temperature of 630°C. A photograph of the specimen after irradiation can be seen in Figure 14. The periodic nondestructive examination of the capsule by neutron radiography showed a maximum fuel elongation of 14%, which occurred at 4.6 a/o burnup. No further change in length occurred throughout the remainder of the irradiation.

The cessation of lengthwise growth in these two specimens is not unusual, as similar behavior has been observed in other metal irradiation specimens where release of the fission gases in the fuel had occurred.⁽⁷⁾

An average increase in jacket diameter of 0.0016 in. was calculated from volume changes determined by an immersion technique. No measurable length change was noted. The jacket was punctured for fission-gas recovery but the gas sample was lost in the hot cell because of equipment failure.

The metallographic examination of the specimen shows that there was no significant penetration of the fuel into the jacket. In isolated areas in the fuel there was occasional evidence of surface reaction occurring to a depth of ~0.005 in. A transverse section of the specimen can be seen in Figure 15. The central area, which is characteristically different from the rest of the fuel, is believed to be (U,Pu₂)Ti + γ phase, which is stable above the temperature of 710°C. Photomicro-

⁽⁷⁾ Beck, W. N., *Irradiations of Uranium-Plutonium Alloys*, ANL-7155, p. 80 (1965).

EI-5768

250X

EI 5766

250X

FIG 13 U 18 *w/o* Pu 14 *w/o* Zr Alloy Jacketed in V 20 *w/o* Ti Irradiated to 12.5 *a/o* Burnup at Maximum Jacket Temperatures of 655°C Photograph at left shows fuel jacket interface and photograph at right the size and distribution of center fuel porosity

EI-5628

FIG 14 U 15 *w/o* Pu 10 *w/o* Ti Alloy Specimen Jacketed in V 20 *w/o* Ti Alloy Tubing after Irradiation to 10.7 *a/o* Burnup at a Maximum Jacket Temperature of 630°C

graphs of the fuel-clad interfaces as well as typical porosity in the specimens can be seen in Figure 16. Additional information as well as design particulars on these specimens are listed in Table 8.

Postirradiation examinations are being conducted on six U-15 *w/o* Pu-12 *w/o* Zr fuel alloy specimens jacketed

severally in Type 304 stainless steel, Type 316 stainless steel, and Hastelloy-X tubing. These specimens were irradiated in an instrumented, temperature-controlled capsule which was inserted in the vertical thimbles of the CP-5 reactor.

Four hours after reactor startup, a temperature

fluctuation was noted on one of the readings for a specimen located in the lower tier. The other five temperature readings remained stable and did so until the specimens had reached 2.4 *a/o* burnup, at which time a temperature excursion of the other two thermocouples in the bottom tier indicated probable cladding failures. The capsule was removed from the irradiation facility and the neutron radiographs showed that the fuel had penetrated the cladding of the three specimens in the lower tier.

The thermocouples adjacent to these specimens, which indicated a maximum jacket temperature of 660°C, had failed to show any increase in temperature that would have caused eutectic formation between the fuel and the cladding (~800°C). Subsequent destructive examination of the three specimens revealed that liquid-phase formation had occurred at the fuel-clad interface. The only available explanation for this occurrence is that a loss of sodium bonding, occurring either in the specimen or immediately adjacent to jacket surfaces, had caused the pins to overheat. Such occurrences would not normally affect the readings of adjacent thermocouples.

The metallographic examination of the three intact upper-tier specimens that operated at maximum jacket temperatures of 600°C showed excellent compatibility between the fuel and the jacket. Photomicrographs of these interfaces are shown in Figure 17. The transverse macrosections of the fuel showed three distinct bands believed to be correlated to phase-transformation temperatures (see Figure 18). The outer zone is believed to correspond to the (α -U + δ + ζ) phase, the second band (α -U + ζ + γ) phase and the central area is principally in the γ phase. The most important reactions are $\gamma + \beta \rightarrow \alpha + \zeta$ at 655°C and $\alpha + \gamma \rightarrow \delta + \zeta$ at 595°C for unirradiated material. As anticipated, the fuel had swelled to the internal diameter of the jacket and the bond sodium was entirely displaced into the gas plenum. Figure 18 also shows that original void volume, which had existed as a sodium-filled annulus around the solid metal fuel pin at the start of irradiation, became redistributed throughout the fuel volume in the form of finely-divided porosity.

A metallographic examination is being conducted on U-15w/oPu-10w/oFz and U-10w/oPu-10w/oFz alloy fuel pins jacketed in Nb-1w/oZr tubing having wall thicknesses between 0.015 to 0.025 in. These specimens had been irradiated to a maximum of 8.7 *a/o* burnup and a maximum jacket temperature of 530°C. The effective fuel density of the specimens was 85.2%. The average fuel volume change within the jacket at the end of the irradiation was found to be 24%. The preliminary macroscopic examination of transverse and

EI-5887

15X

FIG 15. Transverse Section of U-15w/oPu-10w/oTi Jacketed in V-20w/oTi Tubing and Irradiated to 10.7 *a/o* Burnup at Maximum Jacket Temperatures of 630°C.

longitudinal sections of the specimens shows that there was no reaction between fuel and the jacket. The fuel material is characterized by pores approximately 4 μ in diameter near the outer edge. The pores in the center of the rod were approximately 15 μ in diameter. The data for fission-gas recovery indicate that the fuel specimens released from 3.7 to 9.6% of the estimated yield (see Figures 19 and 20).

An irradiation experiment was conducted on vibratorily-compacted U-15w/oPu-10w/oFz powders. The mesh sizes of the powders were -60 +120, -120 +200, or -200 +325 and were contained in Nb-1w/oZr tubing. The powders were sodium impregnated to improve the heat-transfer characteristics of the compact.

A nondestructive neutron examination of the capsule at 1.2 *a/o* burnup indicated that the jackets were intact. A final radiograph taken at 3.8 *a/o* burnup revealed that the compacts had segmented into two or three sections. The destructive examination of the capsule showed the appearance of longitudinal cracks of the cladding in areas where the preirradiation non-destructive examination had indicated the absence of sodium bond.

Twelve U-10w/oPu-10w/oFz and U-15w/oPu-10w/oFz fuel pins jacketed in V-20w/oTi tubing (0.015 in. wall thickness) were irradiated to maximum analyzed burnups of 8.2 *a/o*. The maximum jacket temperatures ranged between 620°C and 630°C. These

FIG. 16. U-15w/oPu-10w/oTi Alloy Clad in V-20w/oTi Irradiated to 10.7 a/o Burnup at Maximum Clad Temperatures of 630°C. Photograph at left shows fuel-jacket interface and photograph at right the size and distribution of center fuel porosity.

TABLE 8. DESIGN PARAMETERS AND OPERATING CONDITIONS FOR SPECIMENS CP-44 AND CP-45

Specimen Number	Design Parameters				Operating Conditions			
	Fuel Composition, w/o	Effective Density, %	Clad. OD, in.	Clad. Thick., in.	kw/ft	Max. Clad. Temp., °C	Max. Fuel Temp., °C	Burnup a/o U + Pu
CP-44	U-15Pu-10Ti	69	0.203	0.015	9.7	630	810	10.7
CP-45	U-18.5Pu-14.1Zr	63	0.208	0.016	12.7	655	840	12.5

specimens represented selected configurations designed to reach predetermined fuel burnups without jacket failures. These configurations were determined by an analytical approach that is described previously.⁽⁸⁾

⁽⁸⁾ Beck, W. N., Murphy, W. F., Kittel, J. H., and Foote, F. G., *Irradiation Behavior of Plutonium Alloy Fuels for Fast Reactors*, Third International Conference on Plutonium, London (November 1965).

The significant conclusion of the results is that the analytical approach is conservative in that the specimens achieved burnups 60% higher than they were designed to reach.

Recent data for fission-gas recovery support the theory that metal fuels will release significant amounts of fission gas after volume increases of approximately 30%. A summary of data pertaining to specimens recently punctured for fission-gas recovery is included in Table 9. A graph of fission-gas release versus fuel-volume increase is shown in Figure 21. The specimens, which were irradiated in capsule CP-39, were designed to determine the fission-gas release from metallic fuels under conditions wherein various amounts of swelling had been permitted. The internal dimensions of the cladding had been calculated to provide a gas plenum pressure of 10 atmospheres all specimens when the fuel had reached the allowable volume increase. The postirradiation examination of the specimen with the smallest allowable volume increase (23%) disclosed that it had a ruptured jacket.

Hastelloy-X Cladding

Type 304
Stainless Steel Cladding

Type 316
Stainless Steel Cladding

EI-5416

250×

EI-5427

250×

EI-5437

250×

FIG. 17. Jacket-Fuel Interface of U-15w/oPu-12w/oZr and Hastelloy-X, Type 304 Stainless Steel, and Type 316 Stainless Steel Irradiated at Maximum Jacket Temperatures of 600°C for 2.4a/o Burnup.

EI-5886

20×

FIG. 18. Transverse Section of U-15w/oPu-12w/oZr Alloy Jacketed in Hastelloy-X. The concentric bands in the fuel were correlated to phase transformation temperatures.

106-9077

11×

FIG. 19. Transverse Section of U-10w/oPu-10w/oFz Alloy Jacketed in Nb-1w/oZr and Irradiated to 7.1 a/o Burnup at Maximum Jacket Temperatures of 530°C.

TABLE 9. RELEASE OF FISSION GAS FROM METAL FUEL SPECIMENS

Specimen Number	Composition, w/o	Maximum Fuel Irradiation Temperature, °C	Burnup a/o Pu + U	Fuel Volume Increase, %	Fission Gas Release, %
33-1	U-10Pu-10Fz	590	7.1	20	3.2
33-6	U-10Pu-10Fz	610	7.1	21	3.7
33-2	U-15Pu-10Fz	610	8.7	26	9.6
23-5	U-20Pu-10Fs	650	1.4	25	14.8
23-6	U-20Pu-10Fs	650	1.4	21	9.2
32-1	U-20Pu-10Fs	690	4.2	25	10.9
32-3	U-20Pu-10Fs	690	4.2	22	8.2
32-4	U-20Pu-10Fs	720	4.2	26	14.1
32-5	U-20Pu-10Fs	720	4.2	22	2.6
32-6	U-20Pu-10Fs	720	4.2	24	4.5
39-2	U-15Pu-10Fz	740	3.0	30	33
39-4	U-15Pu-10Fz	740	3.0	57	63
39-5	U-15Pu-10Fz	740	3.0	97	76
39-6	U-15Pu-10Fz	740	3.0	133	83

EI-5372

250× EI-5371

Jacket

Fuel

250×

FIG. 20. Transverse Section of U-10w/oPu-10w/oFz Alloy Jacketed in Nb-1w/oZr Tubing. The specimen was irradiated to 7.1 a/o burnup at maximum jacket temperatures of 530°C. The photograph at the left shows center porosity as compared to the photograph at the right, which is porosity in the fuel adjacent to the jacket.

44887

FIG. 21 Effect of Fuel Volume Increase on Fission Gas Release.

Those having allowable volume expansions of 30% or greater were intact.

An analysis of the data for specimen irradiation indicates that fission-gas release is largely independent of burnup and irradiation temperature, and depends principally on the amount of fuel swelling. These results and metallographic observations (Figure 22) show that, as the swelling of the specimen approaches 30%, the development of open porosity in the fuel permits the fission gas to escape to the surface.

EI-5767

180X

FIG. 22 Interconnected Porosity Observed in U-18.5w/oPu-14.1u/oZr Alloy, which Had a Measured Volume Expansion of 63% after a Burnup of 12.5 a/o

2. Oxide-Fuel Development

a. PARTICLE - SIZE REDUCTION — DESIGN, CONSTRUCTION, AND OPERATION OF A JAW CRUSHER (J. E. AYER)

The necessity of generating particles of controlled size for the fabrication of vibratorily-compacted fuel bodies has prompted a study of size-reduction techniques. During the fabrication of (U,Pu)O₂ fuel columns for irradiation studies certain needs became apparent. First, a mechanical device to produce particles was needed. It must produce a high yield of acceptable particle sizes to reduce losses and material recycled through fuel reprocessing. Its capacity should be consistent with the criticality limits. The mechanism must be simply constructed for ease of maintenance and cleaning. The manual crushing of ceramic fuel materials showed that a pincer action coupled with shearing, produced the highest yield of desired particle sizes. The above requirements and some screening runs on a prototype machine led to the design of the jaw crusher shown in Figure 23.

The crusher depicted is actuated by an eccentric shaft that provides a pincer movement to the jaws. The shearing action is accomplished by allowing the moveable jaw to slide over its pivot. The motion is preferred to the toggle operation of conventional crushing devices of this type. The jaw spacing is accurately determined by a micrometer. The mechanism is held together by detailed components that can be separated from each other by readily accessible Allen screws. Baffles and gibs prevent the escape and loss of fuel material.

(1) Experimentation

Before the final design of the jaw crusher was undertaken a prototype machine was constructed and operated. The philosophy of prototype operation was to determine the essentials necessary in a mechanism of the type that would be committed to the plutonium gloveboxes. A series of size-reduction runs were made on zirconium dioxide and silicon carbide. The results

FIG. 23. Miniature Jaw Crusher and Feeder.

350-863

sought were the effects of crushing speed, jaw spacing, jaw angle, and ratio of feed particle size to jaw clearance, upon yield of particles within predetermined size ranges.

Since a distribution of particle sizes results from crushing operations a statistical method was chosen to analyze the data. The distribution of particles from each run was defined in terms of average particle size ($\bar{x}$), the standard deviation (σ), skew (α_3) and peakedness (α_4). With such an approach one could state in advance that control of $\bar{x}$ is essential. The standard deviation should be small, resulting in a large peakedness. The factors determining skew should be determined to permit one to take advantage of the asymmetry of the particle size distribution.

(2) Results

Crushing studies on ZrO_2 and SiC revealed that the average particle size yield was influenced most markedly by jaw clearance, and to a lesser extent by crushing speed. With the relationship between jaw clearance and average particle size fixed the elimination of variables became possible. The standard deviation (spread of data) was found to be related to the properties of the material being worked. This factor, then, was uncontrollable within the limits of the experiment. The ratio of feed size to jaw clearance was the controlling variable influencing skew. When this ratio was held between 2 and 3.5 a skew of zero, such as one finds in a normal distribution, resulted. A lower

ratio skewed the distribution to the left; a higher ratio skewed the data to the right. To avoid overworking, the material ratios above 3.5 should be avoided. Peakedness was influenced to the greatest extent by crushing speed—speeds above 80 cycles per minute being detrimental.

(3) Application of Results

The results of the above investigation fixed the design of the operational jaw crusher. Since the effect of jaw angle could not be established, jaws that were parallel at their closest proximity were specified. The crusher speed was fixed at 75 cycles per minute. Jaw clearance was the only variable feature incorporated into the design.

Jaw crusher operation to optimize yield is illustrated in Figure 24. Particles of sizes greater than 10 mesh were used as initial feed, and a particle size range of 0.030 to 0.050 inch is desired. In the initial run the jaw clearance was set at 0.055 inch to maintain a low ratio of feed size (F_s) to jaw clearance (CL) ratio and thus to keep the product distribution skewed to the left, preventing too rapid reduction. The product larger than 50 mils was screened out and recycled around the jaw crusher whose jaw clearance was reduced to 45 mils. This process was repeated and successive passes resulted in the accumulation of the desired product until over 60% of the weight of the product lay within the specified particle size range.

The jaw crusher has been used on Dynapac

350-994

FIG. 24. Cumulative Yield of 30 to 40 Mil Particles by Successive Attrition of 82 Mil ZrO_2 Particles. Jaw speed: 150 cycles per minute.

($\text{UO}_2\text{-PuO}_2$), as processed by Pacific Northwest Laboratory, in accordance with the above program. Typical operation results in a 60% yield of 10/18 mesh oxide, a 26% yield of 20/50 mesh and a 14% yield finer than 50 mesh. The weight distribution for a fuel body of 85% of theoretical density requires 60% to be 10/18 mesh, 17% to be 35/50 mesh and 23% to be less than 325 mesh. It is evident that such requirements are quite easily met by the jaw crusher produced through this development.

b. FABRICATION OF (U,Pu) O_2 FUEL BODIES FOR FAST-REACTOR IRRADIATION STUDIES (J. E. AYER, A. G. HINS, C. F. KONICEK AND G. J. TALABER)

During the past three years we have applied a significant effort to the development of fuel fabrication

by vibratory compaction. The sequence of developmental events has been to (1) determine the effects of particle geometry upon packing, (2) determine the effects of the vibratory mode upon compaction rate and packing efficiency, and (3) apply the above findings to the manufacture of fuel test specimens. The influence of particle geometry upon packing efficiency has been determined.^(9,10,11) The results of investiga-

⁽⁹⁾ Ayer, J. E., and Soppet, F. E., "Vibratory Compaction-Part I, The Compaction of Spherical Shapes," J. Am. Ceram. Soc., 48 (4) pp. 180-183 (1965).

⁽¹⁰⁾ Ayer, J. E., and Soppet, F. E., "Vibratory Compaction-Part II, The Compaction of Angular Shapes," J. Am. Ceram. Soc., 49 (4) pp. 207-210 (1966).

⁽¹¹⁾ U. S. Patent No. 3,261,278, Ayer, James E. and Soppet, Frederick E., "Method and Apparatus for Vibratory Compaction."

TABLE 10. OXIDE-TYPE FUEL-ELEMENT SPECIFICATIONS

No. of Specimens	Column Density, Percent of X-ray Value	Jacket		
		Material	I.D. in mm	Wall thickness in mm
4	80	304	6.43	1.11
4	83	304	6.43	1.11
3	85	304	6.43	1.11
7	80	Hastelloy-X	6.78	0.76
3	85	Hastelloy-X	6.78	0.76
3	80	V-20w/oTi	6.43	1.11

tions into the effect of vibratory mode upon compaction rate are discussed elsewhere in this report. The fabrication of test specimens through application of the results of this development is the subject of this section of the report.

(1) Fuel-Element Description

In October, 1965 the design of a series of 24 experimental oxide-fueled elements for EBR-II irradiations was completed and approved. The packed fuel length was specified as 292 ± 3 mm in Type 304 stainless steel, Hastelloy-X, or V-20w/oTi jackets all with an O.D. of 7.54 mm. The fuel material was Dynapac $\text{UO}_2\text{-20w/oPuO}_2$ as supplied by Pacific Northwest Laboratory. The required fuel-column density was 80, 83, and 85 percent of maximum. The finished length of all rods was 64.14 cm. Table 10 lists physical characteristics of the fuel rods.

The finished fuel specimen was considered acceptable when it was leak-tight and free from alpha contamination. A rod was sufficiently clean when it showed less than 400 dpm direct count and zero wipe count using a proportional alpha counter. Leak-tight was construed as loss of helium from the jacket, under a one kg/cm^2 differential, at a rate less than 2×10^{-6} std cc/sec determined by a helium mass spectrometer leak detector.

(2) Fuel-Element Manufacturing Procedure

(a) Process Development

The loading of the fuel specimens required information on the packing efficiencies and particle densities of each component particle size. Information from previous development work revealed that particle attrition during compaction would modify the packing efficiencies predicted by model systems. To allow prediction of the number and sizes of particle components needed to achieve desired density, a series of

computations based on the mathematical model for angular-particle packing were made. These computer calculations defined the packing efficiency as a function of jacket size, particle size, and number of components. We had found from experience that particle attrition during compaction would raise the packing efficiency between 7 and 10 percent. Calculations of packing efficiencies required to arrive at specified column densities were made by dividing the column density by the particle density. The computer calculations, modified by attrition factors, were then used to determine particle sizes required to meet the fuel column density specifications.

The limit of packing efficiency in two-component systems with brittle particles has been found to be about 86%. In order to reach 85% of full density with particles that are 97.2% dense requires packing efficiency greater than 87%. Efforts to produce uniform density in ternary systems by the infiltration technique have been unsuccessful. The solution, which is incorporated into the computation program, was to blend the two larger-size components. The coarse fraction size was chosen to yield a high packing efficiency; the size of the second component was selected such that it would be small enough to fit into the large voids in the coarse component matrix and large enough so that it could not migrate through the channels between large voids.

(b) Fuel Loading Procedure

The jackets into which the oxide fuel was to be loaded were measured for internal volume by filling with water and determining the quantity contained. This measure was required to compute the particle charge based upon derived packing efficiency. The jackets were then cleaned, dried thoroughly, and wrapped in plastic tape.

The oxide particles, as received from Pacific Northwest Laboratory, were crushed by hand in a Plattner Mortar to the size fractions dictated by the calculations described above. Each batch was sampled for particle density; plutonium, uranium, oxygen, and nitrogen concentration; and isotopic analysis. During particle-size reduction observations of crushing behavior were made in anticipation of specifying the characteristics of a jaw crusher to accomplish this task with greater speed and control. Such a jaw crusher was designed and built during this time and is described in a preceding section (see pages 33 to 35). After screening to size, the charges of coarse and intermediate sized particles were weighed and stored in vials.

All work on the unjacketed oxides was carried out in

the helium-atmosphere glovebox system of the ANL Plutonium Fabrication Facility. The fuel-loading procedure was the same as that previously described.⁽¹²⁾ An abbreviated description follows:

The equipment employed for the compaction of the oxides into metal jackets consisted of an electromagnetic vibrator (Syntron Type V-60) controlled by a rheostat and rectifier. The acceleration impressed during vibration was sensed by an Endevco, Model 2215C accelerometer. The output from the accelerometer was fed into a Hewlett-Packard Model 120B, oscilloscope.

The jackets were attached to the vibrator platen by a stud that was threaded into the bottom plug. After the jackets were attached to the platen a "rattle cage" was dropped over the tube and a funnel was inserted in the open end. The "rattle cage" is a loose-fitting cage, its purpose being to limit bridging of the infiltrating fraction by imparting a random secondary mode of vibration normal to the axial vibration. A primary funnel was used to direct the fuel charge into the tube and to protect the top inside surface of the tube wall from excessive contamination.

Where a three-component mixture was required the preweighed coarse and intermediate-size fuel fractions were mixed thoroughly in a small V-blender. After blending for about 3 minutes the charge was poured into the jacket. During the introduction of the fuel charge the vibrator was running at its lowest setting, which corresponded to a force of 5 g. After the introduction of the fuel charge, the vibrator was stopped and the primary funnel was carefully removed. The care exercised during removal of the funnel was to prevent the funnel from being scraped along the jacket wall and thereby from depositing excessive contamination.

The primary funnel was replaced by a "thimble" and funnel. The thimble, which is essentially a restraining device, is made up of a brass tube soldered into a standard "Swagelok" reducer. The bottom of the brass tube is closed by a screen with mesh larger than the most finely divided fuel fraction and smaller than the coarse fractions. The purpose of the screen is to hold the fuel column in place while the finer fraction is being infiltrated into the bed of coarse particles. O-rings prevent the infiltrating fraction from being conveyed up the fuel-tube wall and subsequent contamination of the fuel-rod hardware.

The addition of the fine fraction was made through the thimble, and was continued as long as the matrix would accept it. This approach required addition of the

fine fraction for up to eight hours while the tube was vibrated at 60 cps and 15 g.

(c) Fuel-Rod Assembly

The thimble was carefully withdrawn and the fuel specimens were partially decontaminated before closure welding to prevent plutonium from being alloyed into the weld bead and permanently contaminating the surface. The jacket was acceptable to welding when surveys showed less than 10 dpm loose contamination and direct count of the jacket-retainer interface showed less than 2000 disintegrations per minute. The closure of a decontaminated fuel element was made by a girth weld that fused the top plug of the retainer to the fuel jacket. The final decontamination was carried out in an air-filled glovebox.

(d) Fuel-Rod Evaluation

The evaluation of the fuel specimens included contamination survey, leak detection and gamma radiography. Completed decontaminated specimens were surveyed directly with a gas-proportional counter. In all cases the loose contamination was less than a total of 10 disintegrations per minute for wipes over the entire surface of the fuel element. Except for isolated cases of contaminated welds, direct survey of the rods showed levels of contamination less than 500 disintegrations per minute.

A helium mass-spectrometer leak test was made at room temperature on all fuel specimens. The element was placed in a chamber that was evacuated by a mechanical pump. When a satisfactory vacuum was attained the chamber was isolated from the vacuum pump and opened to the leak detector. An acceptable specimen showed a leak rate less than 2×10^{-6} std cc/sec.

After cleaning and leak checking, the specimens were radiographed to determine the distribution of the carbides in the fuel column.

(3) Results

Table 11 is a compilation of information on the assembled oxide rods. In this table, SOV is the designation for elements jacketed in 304 stainless steel, HOV represents Hastelloy-X jacketed elements and TVOV stands for vanadium-20w/otitanium alloy jackets. In the twenty-one rods making up the SOV and HOV series the achieved densities came within a total deviation of 1.3%. In the case of the TVOV series an attempt to shorten fabrication time resulted in some bridging.

⁽¹²⁾ "Production of PuC and (U,Pu)C and Fabrication of Carbide Fuel Element Specimens," ANL-7155, Annual Progress Report for 1965 Metallurgy Division, pp. 31-32.

TABLE 11. RESULTS OF COMPACTION OF MIXED-OXIDE IRRADIATION SPECIMENS

Specimen Designation	Particle Charge ^(a)						Packing ^(b) Efficiency	Column Density % of X-ray Value	
	First comp.		Second comp.		Third comp.			Achieved	Desired
	Size	Weight	Size	Weight	Size	Weight			
SOV-1	20/30	60.0	—325	25.0			82.2	79.9	80.0
SOV-2	20/30	60.0	—325	25.0			82.1	79.8	80.0
SOV-3	16/20	61.0	—325	27.5			85.5	83.1	83.0
SOV-4	16/20	61.0	—325	26.3			84.5	82.1	83.0
SOV-5	16/20	61.0	—325	27.6			85.8	83.4	83.0
SOV-6	16/20	61.0	—325	27.6			85.7	83.3	83.0
SOV-7	10/18	53.7	35/50	15.2	—325	21.8	87.6	85.1	85.0
SOV-8	10/18	53.7	35/50	15.2	—325	21.7	86.9	84.5	85.0
SOV-9	10/18	53.7	35/50	15.2	—325	22.1	87.9	85.4	85.0
SOV-10	30/40	60.3	—325	24.5			81.7	79.4	80.0
SOV-11	30/40	60.3	—325	25.0			82.2	79.9	80.0
HOV-1	20/30	65.1	—325	27.1			82.3	80.0	80.0
HOV-2	20/30	65.1	—325	27.1			82.2	79.9	80.0
HOV-3	20/30	65.1	—325	27.1			82.2	79.9	80.0
HOV-4	20/30	65.1	—325	27.1			82.3	80.0	80.0
HOV-6	20/30	65.1	—325	27.1			82.4	80.1	80.0
HOV-8	10/18	56.4	35/50	15.9	—325	25.4	87.4	85.0	85.0
HOV-9	10/18	56.4	35/50	15.9	—325	25.3	87.1	84.7	85.0
HOV-10	10/18	56.4	35/50	15.9	—325	25.3	87.2	84.8	85.0
HOV-11	30/40	65.3	—325	26.8			82.1	79.8	80.0
HOV-15	20/30	65.1	—325	26.6			82.1	79.8	80.0
TVOV-1	30/40	60.5	—325	22.0			79.0	76.8	80.0
TVOV-2	30/40	60.5	—325	23.7			80.8	78.5	80.0
TVOV-3	20/30	60.5	—325	25.2			82.3	80.0	80.0

^a All sizes are U.S. Sieve series; All weights are in grams.

^b Packing efficiencies are based upon particle densities 97.2% of theoretical.

350-830

FIG. 25. Gamma Radiographs of Oxide Fuel Specimens.

Additional studies are underway to further investigate methods to increase infiltration rates.

The quality of the specimens is shown in Figure 25, which is a gamma radiograph of the fuel column in five of the fuel elements fabricated. The manner in which density control is achieved can be seen from this figure. The elements on the extremes, SOV-1 and HOV-15, are lower density (~80%) and made up of the smaller first-component particles. Reducing the size of the first component results in smaller channels and voids in the matrix, thus increasing the resistance to passage of particles of the entering finer fraction and reducing the quantity of material that can enter and be confined in the voids.

SOV-3 (~83% dense) is an example of the effect of

increasing the first component size, an action that reverses the process described above. Further increase in density is brought about by further increase in large component size and the introduction of an intermediate fraction. Such an effect is seen in SOV-7 and HOV-10, which are elements of higher (~85%) density. The partial filling of voids in the positions occupied by the larger particles by the presence of the intermediate fraction offset the additional barriers offered to the infiltrating fine fraction and result in higher density.

The radiographs, which were made after the elements were welded and inspected, show one small chordal crack in the fuel columns in SOV-1 and SOV-3. SOV-7 has large component particles missing from 1/4 inch of the top. The same condition exists for 1/2 inch

HOV-10. HOV-15 is judged a near perfect element. Further development of the vibratory compaction fabrication technique includes inspection of such fuel bodies before welding. During this fiscal year a gamma absorptometer has been constructed to determine, quantitatively, the axial density distribution in a fuel column before welding. This instrument is described in another section of this report.

c. FUEL-PERFORMANCE STUDIES OF URANIUM-PLUTONIUM OXIDES (F. L. BROWN AND L. A. NEIMARK)

Nine encapsulated elements of $\text{UO}_2\text{-PuO}_2$ have been placed in the EBR-II in a program to develop a fuel material to meet the objectives of LMFBR. The fuel material was processed at Pacific Northwest Laboratory by the Dynapac consolidation technique and then powdered and vibratorily compacted into jackets at ANL. The fuel columns, measuring approximately 11.5 in. long by 0.260 in. diameter, were compacted to theoretical densities of 77 to 86%, to provide one of the variables for irradiation. Table 12 lists the elements and their variables in the irradiations.

The study includes the effects of fuel synthesis (coprecipitation, physically-mixed, Dynapac, and sol-gel), fuel form (vibratorily-compacted and pellets), particle shape in vibratory compaction (spheres and angular shapes), and jacket-alloy composition. The fuel includes hypostoichiometry in order to profit from the improvement in thermal conductivity over that of hyperstoichiometric material. The nine elements already exposed in the reactor contain hyperstoichiometric fuel and therefore will be useful for comparison (especially in regard to thermal conductivity) with the same material reduced to hypostoichiometry for later irradiation.

Coprecipitated, pressed and sintered pellets procured from NUMEC and sol-gel material furnished by

TABLE 12. SUMMARY OF VIBRATORILY-COMPACTED HYPERSTOICHIOMETRIC DYNAPAC $\text{UO}_2\text{-20w/oPuO}_2$ IRRADIATIONS IN EBR-II

Cladding			Fuel Column	Irradiation			
Composition, w/o	OD, in.	Wall, in.	Effective density, %	Power density, kw/ft	Max. clad. temp., °C	Target burn-up, a/o	Burn-up accumulated as of 12-31-66, a/o
304 SS	0.297	0.020	82	16.3	555	2	2.7 ^(a)
304 SS	0.297	0.020	82	17.1	565	2	2.9 ^(a)
304 SS	0.296	0.019	80	19.9	590	5	3.0
304 SS	0.296	0.019	83	21.7	610	5	3.1
304 SS	0.296	0.019	85	23.4	630	5	3.0
Hast.-X	0.295	0.014	80	21.1	590	5	2.9
Hast.-X	0.295	0.014	80	22.5	600	5	3.1
Hast.-X	0.295	0.014	86	23.7	615	5	2.9
V-20Ti	0.297	0.020	77	20.8	575	5	3.0

^(a) Burnup at time of discharge.

ORNL will be compared with the hyper- and hypostoichiometric Dynapac material furnished previously by Pacific Northwest Laboratory.

The first two elements of vibratorily-compacted mixed powders in Type 304 stainless steel, as shown in Table 12 completed their scheduled exposure near the end of the year and were discharged at calculated burnups of 2.7 and 2.9 a/o. The capsules containing these two elements were shipped to the Juggernaut reactor for neutron radiography preparatory to decanning in the Metallurgy Alpha-Gamma Hot Cell. The radiographs indicate that: (a) both elements are intact, (b) the axial growth of both fuel columns is insignificant, and (c) axial voids approximately 0.06 in. in diameter developed throughout most of the length of both fuel columns.

3. Carbide-Fuel Development

a. FABRICATION OF $(\text{U,Pu})\text{C}$ FROM MIXED-CARBIDE POWDERS DERIVED FROM THE METAL ALLOY BY A HYDRIDE-CYCLE/HYDROCARBON ROUTE (S. STRAUSBERG AND T. W. LATIMER)

Characterization and fabrication studies were carried out with mixed $(\text{U}_{0.85}\text{Pu}_{0.15})\text{C}_{1+x}$ powders prepared by a fluidized-bed technique (Chemical Engi-

neering Division). The powders were produced from arc-melted alloys of uranium and plutonium which were hydrided, decomposed and then converted to carbides by cyclic reaction with methane- H_2 mixtures.

Susceptibility to contamination by gaseous impurities in the atmosphere of a Metallurgy Division glovebox (~ 50 ppm O_2 and 100 ppm H_2O vapor) was checked on a powder sample exposed to the box environment. After one month a weight increase of $\sim 0.7\%$

TABLE 13. FABRICATION OF $(U_{0.85}Pu_{0.15})C_{1+x}$ PELLETS FROM MIXED-CARBIDE POWDERS PRODUCED BY HYDRIDE CYCLE ON $(U_{0.85}Pu_{0.15})$ METAL ALLOY, FOLLOWED BY HYDROCARBON SYNTHESIS

Compaction Pressure, Tonne/cm ²	Ni Added, %	Green Density, g/cc	Sintered Data					Analytical Results ^(a)		
			Temp., °C	Wt. loss, %	Volume shrinkage, %	Pellet, g/cc	Density, % T.D. ^(b)	Carbon, %	Oxygen, ppm	N ₂ , ppm
2.12	0	7.21	1550	0.87 ^(c)	39.9	11.76	86.4	—	—	—
4.23	0	7.83	1550	0.57 ^(c)	37.5	12.45	91.5	4.88 ^(d)	1700 ^(d)	1600 ^(d)
6.35	0	8.08	1550	0.57 ^(c)	35.1	12.38	90.9	—	—	—
2.82	0	7.53	1650	0.60	37.9	12.01	88.3	—	—	—
4.23	0	7.90	1650	0.61	37.5	12.46	91.6	4.90	2200	520
6.35	0	8.31	1650	0.50	34.3	12.58	92.4	—	—	—
2.82	0	7.47	1900	0.64	39.0	12.18	89.5	—	—	—
4.23	0	7.78	1900	0.57	37.0	12.27	90.1	4.86 ^(d)	1600 ^(d)	1700 ^(d)
6.35	0	8.21	1900	0.58	33.9	12.35	90.7	—	—	—
2.12	0.2	—	1550	— ^(c)	32.8	10.01	73.5	Residual Nickel, ppm 1370		
4.23	0.2	7.78	1550	0.79 ^(c)	28.3	10.77	79.2			
6.35	0.2	8.26	1550	0.72 ^(c)	27.8	11.18	82.2			
2.82	0.2	7.59	1650	0.83	33.1	11.24	82.6	2000		
4.23	0.2	7.87	1650	0.62	31.9	11.49	84.4			
6.35	0.2	8.27	1650	0.59	30.6	11.83	86.9			
2.82	0.2	7.40	1900	0.82	38.0	11.84	86.9	1620		
4.23	0.2	7.81	1900	0.73	34.9	12.02	88.3			
6.35	0.2	8.23	1900	0.72	34.0	12.17	89.4			

^(a) Original analyses on carbide powders, obtained from Chem. Engineering Division personnel, indicated 4.89% C, 490 ppm O₂ and 700 ppm N₂. All analyses are reported on a weight basis.

^(b) Based upon 13.61 g/cc, a "weighted" average of the theoretical monocarbide densities, i.e., "X-ray densities" of carbides with a defect-free lattice, of mixed carbides containing ~15% Pu.

^(c) Questionable data due to poor quality of compacts, resulting in physical chipping, etc.

^(d) These analyses obtained on same day, ~5 weeks after fabrication; remaining analyses shown in this report determined more than two months after fabrication.

was found, which did not change on subsequent exposure. Densification tests of this powder gave a pour density of ~3.1 g/cc and a tap density of ~4.5 g/cc. Vibration of the powder through screens for a few minutes produced the following sieve analysis based on the U. S. Standard sieve system: 20.5% +200, 21.1% -200 +325 and 53.4% -325 mesh.

Pellet fabrication was carried out by conventional techniques, i.e., intimate mixing of powder with binder (0.5% Carbowax solution in alcohol), cold compaction in a hardened steel die (0.711 cm diameter) with a Carver press and sintering in a tantalum resistance furnace under low-flow (~15.7 cc/sec) high-purity argon at a slight positive pressure. Presintering (for binder removal) was carried out at increasing temperatures to ~900°C; the furnace was maintained at this temperature overnight and sintering was completed on the next day by use of a two hour soak at the peak temperature. The effect of nickel was evaluated in early tests through addition of 0.2 w/o nickel powder (-400

mesh) at the binder-addition stage. Typical fabrication results are shown in Table 13 for a series of tests that evaluate the effects of compacting pressure, Ni addition and sintering temperature.

The data obtained from three sintering runs, based upon averages from two pellets (but only one analysis), indicate the powder is moderately sinterable. Our results show that pellets of reasonable density may be sintered at temperatures as low as 1550°C. The optimum sintering temperature for maximum density appears to be 1650°C (when no nickel is used). Lower densities accordingly result at 1900°C, but when nickel is added greater densities are achieved at the high sintering temperatures. As indicated, the nickel powder does not behave as a sintering aid. The presence of nickel actually hinders densification, for significantly lower densities are obtained than in pellets prepared without nickel.

Densification studies showed that the optimum compaction pressure was ~4.23 tonne/cm². Compacts

pressed at 2.12 tonne/cm² had insufficient green strength and pressing became somewhat difficult at pressures above 6.35 tonne/cm².

Weight losses were reasonable considering the 0.5 w/o addition of Carbowax and minor amounts of stearic acid from lubrication of the die. The weight loss data indicate no loss of plutonium at sintering temperatures of 1550°, 1650°, or 1900°C (see Table 14).

Oxygen and nitrogen contamination result from long storage times of the unprotected powder as well as pickup in the pellets after fabrication, prior to analyses. The analyses indicate equivalent carbon contents of 5.11 to 5.14 w/o. These results agree with metallographic structures, which show appreciable second-phase sesquicarbide content. Photomicrographs of typical pellet structures are shown in Figures 26 to 29.

TABLE 14. TYPICAL Pu ANALYSES OCCURRING DURING THE FABRICATION OF HYDRIDE-DERIVED MIXED CARBIDES

Original U-Pu Metal Alloy, w/o Pu	As-Prepared Mixed Carbide Powder, w/o Pu	In Pellets, Sintered at These Temperatures, w/o Pu		
		1550°C	1650°C	1900°C
15.1	14.15	14.23 ^(a)	14.12	14.23 ^(a)

^(a) These samples analyzed at the same time; remaining sample (from 1650°C sinter) analyzed about two months later.

45823

185×

FIG. 27. Hyperstoichiometric (U,Pu)C + 0.2 w/o Ni Fired at 1650°C. (Orthophosphoric etch.)

45825

185×

FIG. 26. Hyperstoichiometric (U,Pu)C Fired at 1650°C. (Orthophosphoric etch.)

45817

200×

FIG. 28. Hyperstoichiometric (U,Pu)C Fired at 1900°C. (Orthophosphoric etch.)

45819

200×

FIG 29. Hyperstoichiometric (U,Pu)C + 0.2 w/o Ni Fired at 1900°C. (Orthophosphoric etch.)

Structures obtained in pellets sintered at 1500° or 1650°C were essentially identical; however, when sintering was carried out at 1900°C, sesquicarbide migrated to the monocarbide grain boundaries (see Figures 27 and 28). Pellets made from powders that contained nickel additive showed minor evidence of

Widmanstatten lines (typical of an MC₂ structure) when sintering was carried out at 1900°C. The MC₂ structure was not evident in pellets with nickel addition sintered at lower temperatures or in pellets without nickel sintered at the temperatures indicated in Table 13.

Attempts were made to prepare pellets with densities of ~85 theoretical, in accordance with current interests for fast-reactor fuels. Two techniques of reducing the density of the sintered pellets were investigated: (1) the binder content was increased, and (2) the powder was prefired under vacuum in an attempt to reduce its sinterability. As shown in Tables 15 and 16, reductions in pellet density were negligible by either of these techniques (all compacts were pressed at 4.23 tonne/cm² with 0.5% Carbowax, unless denoted otherwise). The data represent an average taken from four pellets at each condition (except for analyses). In these tables T.D. refers to the density determined by the X-ray examination of an ideal specimen.

The deleterious effects of powder contamination, due to O₂ and/or H₂O "pickup", were large reductions in carbon content (removal as CO) and high oxygen levels. The removal of carbon caused approximately twice the usual weight loss of the pellets and a reduction of ~3 to 4% in their densities. Storage in a vacuum desiccator for about five weeks did not change the behavior of the carbide powder.

The addition of nickel (0.2 w/o) to these powders is a convenient technique for manufacturing low-density (~85% T.D.) pellets from the mixed-carbide powders. This addition, however, will introduce a slight nickel contamination in the fabricated pellets.

TABLE 15. EFFECT OF VARIABLE BINDER CONTENT (CARBOWAX) ON THE FABRICATION OF (U,Pu)C_{1+x} PELLETS FROM MIXED-CARBIDE POWDERS PRODUCED BY THE HYDRIDE-CYCLE/HYDROCARBON ROUTE

Binder Content, %	Green Density, g/cc	Sintered Data					Analytical Results		
		Temp., °C	Wt. Loss, %	Volume shrinkage, %	Density		Carbon, %	Oxygen, ppm	N ₂ , ppm
					g/cc	% T.D.			
1/2	7.91	1650	0.58	36.9	12.43	91.2	4.95	2800	380
1	7.99	1650	0.83	36.6	12.50	91.7	4.96	2700	420
2	8.10	1650	2.04 ^(a)	33.3 ^(a)	11.89 ^(a)	87.3 ^(a)	4.93	3000	410
1/2 ^(b)	7.89	1650	1.11	34.3	11.88	87.2	4.64	3800	380
1/2	7.92	1900	0.58	36.6	12.41	91.1	—	—	—
1	8.01	1900	1.00	35.7	12.36	90.7	—	—	—
2	8.13	1900	1.80	34.9	12.27	90.0	4.89	3300	260
1/2 ^(b)	8.06 ^(c)	1900	1.28	33.7	12.01 ^(c)	88.1 ^(c)	4.57	6000	280

^(a) Not representative since pellets severely cracked and distorted; in the subsequent run a longer presintering time was used and no difficulties were encountered.

^(b) These single compacts prepared from *exposed* powder sample (~0.7% wt. gain).

^(c) Compact repressed, resulting in "higher-than-normal" green and sintered density.

TABLE 16. EFFECT OF POWDER PRE-FIRE TEMPERATURE ON THE FABRICATION OF (U,Pu) C_{1+x} PELLETS FROM MIXED-CARBIDE POWDERS PRODUCED BY HYDRIDE-CYCLE/HYDROCARBON ROUTE

Powder Pre-Fire Temp., °C	Green Density, g/cc	Sintered Data					Analytical Results		
		Temp., °C	Weight Loss, %	Volume Shrinkage, %	Density		Carbon, %	Oxygen, ppm	N ₂ , ppm
					g/cc	% T.D.			
None ^(a)	8.06	1650	0.77	34.4	12.19	89.6	—	—	—
1000	8.04	1650	0.84	35.6	12.45	91.4	4.80	3600	540
1200	8.26	1650	0.66	33.7	12.39	91.0	4.85	3400	74
None ^(a)	7.95	1900	0.88	34.9	12.10	88.9	—	—	—
1000	8.04	1900	0.88	34.7	12.19	89.6	—	—	—
1200	8.21	1900	0.73	33.8	12.31	90.4	4.71	3600	1100

^(a) But prepared at 800°C, with CH₄-H₂, during synthesis.

b. METAL ADDITIONS TO HYPERSTOICHIOMETRIC (U,Pu)C (T. W. LATIMER)

Although single-phase uranium-plutonium monocarbide appears to be a desirable fast-reactor fuel material from the standpoint of compatibility with cladding materials, technology, as yet, has not been developed to produce this material on a large-scale basis. Possibly the best tolerances now attainable would be no less than ± 0.1 w/o carbon. For this reason, it appears that compositional modifications to hyperstoichiometric carbides may be necessary to minimize harmful effects by the higher-carbide phases on cladding materials, especially in the presence of liquid sodium.

Three metals—Cr, Mo, and W—were selected as the ones most likely to react with the higher carbides to form more stable compounds without reducing the monocarbide. Phase studies in the U-Cr-C, U-Mo-C, and U-W-C systems show the existence of ternary compounds UCrC₂, UMoC₂, and UWC₂.

Hyperstoichiometric (U,Pu)C containing 5.20 w/o C and 0.03–0.04 w/o O + N was prepared by arc-melting. Chromium, molybdenum, and tungsten powders (-37μ) were added in amounts of 3.0 w/o, 5.5 w/o, and 10.5 w/o, respectively, to the -44μ carbide powder prepared from the arc-melted buttons. These percentages were based on the amount necessary to react with (U,Pu)₂C₃ and (U,Pu)C₂ in material containing up to 5.45 equivalent w/o C to form (U,Pu)XC₂ (where X = Cr, Mo, or W).

In addition, some pellets were made containing Ni, a common sintering aid for (U,Pu) carbide powders. These mixtures were sintered at 1700°C for three hours and at 1900°C for two hours in a flowing argon atmosphere.

Sintered densities of the pellets are listed in Table 17. The addition of Ni effects some densification in

TABLE 17. GEOMETRIC DENSITIES OF HYPERSTOICHIOMETRIC (U,Pu) CARBIDE (5.2–5.3 w/o EQUIVALENT CARBON) WITH METAL ADDITIONS

Wt. %	1700°C (3 Hrs)	1900°C (2 Hrs)
No addition	11.0	11.8
0.1 Ni	11.5	11.8
0.2 Ni	11.6	11.7
0.4 Ni	11.8	11.6
3.0 Cr	10.2	10.8
3.0 Cr + 0.4 Ni	10.6	—
5.5 Mo	10.7	11.6
5.5 Mo + 0.4 Ni	10.7	11.5
10.5 W + 0.4 W	11.6	12.4

the (U,Pu) carbide powder at 1700°C but at 1900°C tends to slightly lower the density because of excessive grain growth.

A greater degree of homogeneity accompanied the increase in densities of the compositions containing Mo and W sintered at 1900°C compared with those sintered at 1700°C. Microstructures of these two compositions sintered at 1900°C are shown in Figures 30 and 31.

Although the composition containing Cr was more dense at 1900°C than at 1700°C, the homogeneity of the structure was destroyed and the pellets had a tendency to stick to the tungsten setter plate. This effect was also observed at 1700°C in the composition that contained 0.4 w/o Ni in addition to 3.0 w/o Cr. The microstructure of this composition (without the Ni addition), sintered at 1700°C, is shown in Figure 32.

The addition of each of the three metals to the (U_{0.8}Pu_{0.2}) carbide powder produced a two-phase structure. The matrix in each case was (U,Pu)C with only a slight amount of either Cr, Mo, or W found in this phase. Uncorrected intensity ratios from electron

44018 200×
FIG. 30. Hyperstoichiometric (U,Pu)C with Mo Addition
Fired at 1900°C. (Orthophosphoric etch.)

43953 200×
FIG. 32. Hyperstoichiometric (U,Pu)C with Cr Addition
Fired at 1700°C. (Orthophosphoric etch.)

44020 200×
FIG. 31. Hyperstoichiometric (U,Pu)C with W Addition
Fired at 1900°C. (Orthophosphoric etch.)

microprobe analysis indicate a metal content of about 1.7w/oCr, 0.6w/oMo and 1.6w/oW.

The second phases in the three samples have not as yet been identified by X-ray analysis, but some analysis was made through use of the electron microprobe. The "second phase", in the case of the Cr-samples sintered at 1700°C, was shown to be of a variable composition with three separate composition zones observed in many areas. Approximate ratios of U, Pu and Cr (uncorrected for absorption or atomic number effects) in these zones, which indicate the extent of the compositional variation, are given in Table 18.

The second phases in the Mo and W samples sintered at 1900°C were of uniform composition. The weight ratio of W to (U,Pu) in the second phase (0.80)* was found to be close to the theoretical ratio for $(U_{0.8}Pu_{0.2})WC_2$ (0.77), but the ratio of Mo to (U,Pu) in the second phase of the other sample (0.59)* was significantly greater than that in $(U_{0.8}Pu_{0.2})MoC_2$ (0.40). The U:Pu ratios of the matrix and the second phase of the three sets of specimens are shown in Table 19. Chemical analyses will be made

* Corrected for absorption by method outlined in "Absorption Correction Tables for Microprobe Analysis" by J. W. Colby and J. F. Niedermeyer (NLCO-914) October 1964.

to confirm the overall U and Pu contents and to compare them with those from the unmodified composition.

c. PREPARATION OF (U,15w/oPu)C FOR VIBRATORILY-COMPACTED FUEL

(R. E. MAILHOT AND O. L. KRUGER)

Uranium-plutonium monocarbide is being investigated as a fast-reactor fuel at ANL. These studies include irradiation of both sintered pellets and vibratorily-compacted powders. The techniques for preparation of the pellets have been given in a previous progress report.⁽¹³⁾ Initial studies of vibratorily-compacted fuel were conducted with physically mixed powders of UC and PuC. Recently, 3 kg of high-density stoichiometric (U,15w/oPu)C has been prepared to continue this work.

Previous work had shown that the arc-melting process produces homogeneous material with a reproducible carbon composition and low oxygen content on a laboratory scale. Therefore, this technique was used to prepare 50 gm buttons of (U,15w/oPu)C. The melts were kept small to avoid appreciable contamination from the tungsten electrode. The time in the liquid state was kept short to avoid detectable plutonium losses. Chemical analyses for carbon and oxygen were taken of random samples. These results are given in Table 20. As expected, the carbon contents of the arc-melted buttons were all very close to stoichiometric and the oxygen contents were less than 0.03 w/o.

d. SYNTHESIS OF URANIUM-PLUTONIUM MONOCARBIDE SOLID SOLUTION BY REACTION SINTERING

(D. E. WHITE AND J. H. HANDWERK)

Work on the synthesis of a solid solution of (U,Pu)C by reaction sintering was continued in an effort to increase the density and to control the stoichiometry of the sintered compacts. Mixtures of uranium dicarbide, uranium hydride and plutonium hydride were preformed into pellets and the pellets were isostatically pressed at 3515 kg/cm². The pellets were sintered in an atmosphere of flowing argon to 1900°C, and the peak temperature was held for three hours.

The pellets produced were free of visible defects. Geometric density as calculated from pellet dimensions was found to average 11.07 g/cc or about 81.4% of theoretical density.

Chemical analysis indicated no loss of plutonium, however, the carbon content was in excess of the stoichiometric amount by 0.28 w/o. Oxygen and nitro-

TABLE 18. WEIGHT RATIOS^(a) OF THE COMPOSITIONAL ZONES FOUND IN THE Cr-CONTAINING "SECOND PHASE"

	U	Pu	Cr
1st Zone	62	13	25
2nd Zone	40	17	43
3rd Zone	15	6	79

^(a) Based on 100 parts by weight total and excluding carbon content.

TABLE 19. U:Pu RATIOS OF THE PHASES PRESENT IN THE Cr, Mo, AND W-CONTAINING SPECIMENS

Metal Additions	U:Pu Weight Ratio (Microprobe)	
	Matrix	Second phase
Cr	4.6	4.8, 2.4 & 2.3
Mo	4.0	5.8
W	4.5	4.6

TABLE 20. CHEMICAL ANALYSIS OF (U,15Pu)C ARC-MELTED BUTTONS

Melt No.	Carbon, %	Oxygen, ppm	Nitrogen, ppm
1	4.78	29	71
2	4.67	177	179
3	4.88	286	490
4	4.73	26	147
7	4.63	—	—

gen contamination was found to be 950 and 790 ppm, respectively. X-ray diffraction and metallographic analysis indicated a second phase of (U,Pu)₂C₃. This sesquicarbide phase was estimated to be 5-6 w/o.

e. STUDIES OF RATE OF ENTRY IN VIBRATORY COMPACTION

(J. E. AYER, F. E. SOPPET AND R. C. FRANK)

The purpose of this program is to find an economical and simple method of fabricating entire fuel-element assemblies. Particulate fuels were chosen as the basis for the study. To conserve on costly compounds of uranium and plutonium and to simplify handling requirements, preliminary experiments were carried out on blast-cleaning shot and grit. A three-part study of the packing characteristics of spherical and angular particles has resulted from this interest. During this year the third part of the study, the factors influencing rate of compact formation was started.

The experiments with spherical particles showed that an infiltration technique was a solution to separation of particles of different size caused by the levitation of the larger size by the smaller compo-

⁽¹³⁾ Annual Report for 1964, Metallurgy Division, ANL-7000, p. 15.

nent.⁽¹⁴⁾ This technique, considered to be tantamount to the uniform distribution of particles in a column, was employed in the rate-of-entry study. The rate of entry of particles into a matrix of larger particles was found to be influenced by frequency of vibration, acceleration, the void fraction in the matrix, column height, and ratio of sizes of entering to matrix particles. The specifics of the study are as follows:

(1) Drawing Force

The rate of entry of particles of constant diameter ratios into a matrix of fixed void fraction was found to respond to variations in the frequency and acceleration of impressed vibration. Infiltration time for both spherical and angular particles decreased with increasing acceleration to about 15 g's. Between 15 to 20 g's the observed difference in the time was so small as to suggest that a plateau is reached in the rate of infiltration between these two values. The influence of frequency on infiltration time showed a minimum, for all accelerations to 20 g's, between 40 and 80 cycles per second. (This fact had been suggested by screening experiments and 60-cycle vibration has been used in the fabrication of fuel columns of carbides and oxides for irradiation testing.) The minimum is depressed as acceleration increases and in the case of spherical particles is quite low. In all cases, at driving frequencies between 100 and 400 cycles per second, infiltration time increases with increasing frequency.

(2) Column Characteristics

The infiltration time of a smaller component varies inversely with the void fraction in the matrix. The relationship varies exponentially with the void fraction. In simple terms this implies that as the void fraction becomes small the void size becomes small and the entering particle must be allowed additional time to seek out and fill the increased number of smaller holes.

The rate of infiltration is also influenced by the ratio of the sizes of matrix particles to infiltrating particles. Actually the relationship should be governed by the ratio of the size of the infiltrating particle to that of the void but, since the voids are connecting and continuous and depend for their size upon the matrix particle size, the stated ratio is preferred. The influence in both spherical and angular particles is somewhat hyperbolic. When the ratio of particle sizes is a minimum, below which infiltration cannot proceed, the rate is low. As the ratio increases infiltration becomes faster until a maximum is reached. For spherical particles the minimum ratio of larger to smaller component to

allow infiltration is about five; but for angular particles this value is about seven. The maximum infiltration rate for spheres is reached when the size ratio is greater than eleven. Angular particles respond to increases in size ratio above 18.

Finally the influence of column height upon infiltration rate was studied. This was done to gain some insight into the mechanism of "hole filling." Our findings indicate that a nearly straight line relation between column height and infiltration time exist for the first two-thirds of the time required. This would indicate that at first the column fills as water, flowing at a constant rate, fills a vessel. This is, of course, an over-simplification neglecting, among other factors, the resistance to flow offered by the matrix particles. For the last third of the filling time the rate changes while the local particles settle into voids not occupied during the initial and incomplete filling period. During this latter period we have observed that about 80 percent of the void space has been filled and the additional time is required to infiltrate the more inaccessible voids.

The above work is subject to verification, which requires instrumentation to determine the extent of void filling. The quantities of infiltrating component were determined from mathematical relationships reported in previous studies.^(14, 15) Since the curve fits are made on a least-square basis a standard deviation exists that could reflect the incomplete filling of voids and channels and alter the above results. A gamma absorptometer recently constructed to determine the axial distribution of vibratorily-compacted fuels in a rod will be "checked out" by attempts to confirm above results.

(3) Gamma Absorptometer

The gamma absorptometer built during this year is shown in Figure 33. The design criteria were that the device should be installed in the gloveboxes of the Plutonium Fabrication Facility to allow examination of fuel rods before closure. The source and shielding should support scanning of small-diameter rods with minimum of time and massive equipment. High resolution and density discrimination was necessary. Finally, the read-out and read-in equipment should be capable of insertion of standards for comparison, recall of data, and amenable to recording the character of an inspected element. These requirements are satisfied by the device shown.

The absorptometer consists of a fuel-element drive mechanism, a scanning head, and reading equipment.

⁽¹⁴⁾ Ayer, J. E. and Soppet, F. E., "Vibratory Compaction—Part I, The Compaction of Spherical Shapes," *J. Am. Ceram. Soc.*, **48**(4), 180-183, (1965).

⁽¹⁵⁾ Ayer, J. E. and Soppet, F. E., "Vibratory Compaction—Part II, The Compaction of Angular Shapes," *J. Am. Ceram. Soc.*, **49**(4), pp. 207-210 (1966).

The fuel-element drive mechanism is a modification of a 6-inch lathe. The scanning head, which is mounted on the lathe cross feed, contains shielding, a collimator and shutter, a thulium-170 source, and a scintillation counter with a photomultiplier tube, amplifier and NaI crystal. The scanning speed is 13.3 cm per min. and the rod rotation is 100 rev. per min. Four shutter apertures of 1.6, 3.2, 4.8, and 6.4 mm width and 4.8 mm length are available. Bench top tests of the configuration used in the final design gave indication that density changes of less than 2 percent in 6.35 mm thicknesses of UO_2 could be detected. The reading equipment consists of a 400-channel pulse-height analyzer with live display of data accumulation on an oscilloscope. The analyzer system is complete with read-out and read-in capability. Read out is of the teletype tape variety such that recall for display and comparison with immediate data accumulation is possible through the read-in function.

f. DEVELOPMENT OF PROCESS EQUIPMENT FOR CERAMIC FUELS (A. B. SHUCK AND G. J. POKORNY)

An inert-atmosphere glovebox that encloses 480 feet³ of space was installed and equipped for ceramic fuel fabrication. The glovebox line is shown in Figure 34. Three double-module gloveboxes each 12 feet wide by 6 feet high are used in an 18-foot train attached to the conveyor. The end box sits on a 40 inch deep well to the floor giving 9 feet of head room to the bottom of the craneway. The two other double-module boxes sit upon a cabinet base that encloses the vacuum pumping system.

The equipment installed in this glovebox line is a tungsten-element furnace and a plasma-reaction chamber. The tungsten furnace has been tested at temperatures of 2700°C in a vacuum, and 2500°C with one-atmosphere pressure of helium gas. The furnace, shown in Fig. 35, is of the cold-wall design. It is heated by four 3-phase tungsten-wire-mesh heating elements within reflective heat shields. The heat shields, which are made of seven layers of thin tungsten sheet, are supported in a water-cooled copper box within the vacuum chamber. The exterior shell of the furnace is a double-walled stainless steel tank with coolant water between the tank walls. The tank axis is horizontal and access to the furnace is by identical front and back doors each of which carry a set of tungsten-mesh heating elements and heat shields. The doors must move outward along the furnace axis about 5 inches for the heater elements to clear. This is facilitated by drawing the door outward on two tracks to a position where it may be picked up and moved sideways in the hood by an electrically operated hoist. The furnace was de-

350-939

FIG 33. Gamma Absorptometer, Multichannel Analyzer and Teletype Printout.

350-911

FIG. 34. Glovebox PF-15 with Tungsten Element Furnace and Plasma Chamber.

350-913

FIG. 35 Tungsten-Element Assembly as Installed in the High-Temperature Furnace.

signed so that all parts are accessible from the glove-ports for maintenance and for changing the elements and heat shields. The heater box is cooled by four parallel water circuits, each of which is connected to its own flow meter. A single water circuit is provided in each of the door panels. Electrical power is conducted to the heating element through water-cooled feedthroughs in the furnace shell and in the glovebox from a 100-kw saturable-reactance transformer.

The aqueous precipitation methods in making oxide and the gas phase reaction methods of making carbide reactor fuels produce fine low-density powders. Several processing methods have been used to convert these powders at Hanford, granulating and sintering, pelleting and sintering, and various fusion processes. The products of these processes are massive and must be crushed and size classified for vibratory compaction. Crushing produces an angular product that is not ideally suited for vibratory compaction. Dusting losses and the need to recycle the fine materials add to the processing costs.

The vibratory compaction of spherical powders has been shown to have many potential advantages, but economical methods have not been developed to produce the spherical powders, and work on vibratory compaction has been suspended. The reaction chamber shown in Figure 36 was, however, designed to develop a variety of arc-plasma and induction-coupled plasma devices for spheroidizing ceramic fuels such as $(U,Pu)O_2$ and $(U,Pu)C$. This chamber consists of a spherical section, 28 inches in inside diameter, mounted on top of a cylindroconical chamber that is 18 inches in diameter by 40 inches deep. The spherical section is equipped with five 10 inch flanges to which a variety of plasma-generating devices may be mounted. The unit has been initially equipped for processing with a high-intensity arc and with a cavity-arc plasma torch. Installation of an induction-coupled plasma torch upon the equipment is planned for the future. The equipment will be tested for the semicontinuous fusion of granulated and powdered $(U,Pu)O_2$ and $(U,Pu)C$. Exploratory work was also done on the synthesis of $(U,Pu)C$ from $(U,Pu)O_2$ and carbon by the arc-fusion methods.

Auxiliary equipment on this glovebox line consists of a dual 6 inch diffusion pumping system located in the cabinet beneath the gloveboxes, a 600-ampere welding generator, and a closed coolant system for the furnace and reaction chamber. Each circuit of the cooling system is metered and fully alarmed. The coolant system contains a maximum of about 20 gallons with heat exchange to the Building 350 positive pressure chilled water system. Positive pressure is used instead of negative pressure to pump coolant through

350-912

FIG. 36. Plasma Chamber Equipped with Consumable Electrode Arc.

this system to provide an adequate flow to the high temperature furnaces and plasma devices.

A second glovebox line, shown in Fig. 37, was converted from air to argon atmosphere and equipped for carbide pellet making. This line encloses 190 feet and is free standing. Conversion to argon atmosphere consisted of adding an argon purifying and analyzing system. The atmosphere is circulated through a platinum catalytic reactor, where the oxygen is combined with hydrogen, and through molecular sieves to remove the moisture. The analytical instruments are an electrolytic oxygen analyzer and a phosphorus pentoxide moisture analyzer. The line is equipped with blending and milling equipment, a 20-ton hydraulic press, a

350-910

Fig. 37. Glovebox Line PF-23 with Argon Atmosphere and Carbide Pellet Fabricating Equipment.

vacuum drying oven, and a carbon-tube resistance furnace capable of 2000°C operation. This line went into operation in November, 1966.

g. COMPATIBILITY OF STOICHIOMETRIC AND HYPERSTOICHIOMETRIC CARBIDES WITH POTENTIAL JACKET MATERIALS
(T. W. LATIMER)

The substitutional solid solubility of oxygen and nitrogen impurities for carbon in the (U,Pu)C structure effects the range of composition wherein this compound is single-phase. For this reason, the effect of the oxygen and nitrogen impurities was taken into consideration in preparing the mixed carbide specimens. Two carbide compositions, one containing 4.83 *w/o* equivalent carbon (single-phase) and the other containing 5.25 *w/o* equivalent carbon (approximately 21 *v/o* (U,Pu)₂C₃), were tested with a series of iron-, nickel-, and vanadium-based alloys in the temperature range 700°C to 900°C. The uranium to plutonium

ratio of both fuel compositions was 4:1. The compatibility test assemblies and the chemical compositions of the alloys tested have been previously described.⁽¹⁶⁾

The extent of interaction, as determined by metallography, at the fuel-cladding interface in the compatibility couples tested for 42 days (1008 hours) is summarized in Table 21 for the alloys in which no more than one reaction zone was observed. Tables 22 and 23 summarize the extent of reaction with Inconel 625 and with two vanadium alloys, respectively.

The band which appears in the etched samples of Type 304 SS after contact with the hyperstoichiometric (U,Pu)C is shown in Figure 38. In studies that are not yet complete an electron-microprobe analysis has shown a gradual carbon gradient from the interface beyond this band.

Examination of specimens heat-treated at 1100° for seven days has shown that particles of high ura-

⁽¹⁶⁾ *Annual Report for 1965, Metallurgy Division, ANL-7155, pp. 25-29.*

niun and plutonium content are present in the stainless steel at the interface. The presence of such particles could explain the melting previously reported⁽¹²⁾ to have occurred sometime in an interval of 17 to 42 days during a compatibility test.

The extent of the reaction at 800°C with Hastelloy-X appears to be unaffected by the presence of the sesquicarbide phase. This reaction is shown in Figure 39. The major portion of the reaction zone was noted on the fuel side and has a nickel content slightly higher than Hastelloy-X. The Pu-to-U ratio in this zone appears to be higher than that of the base fuel composition. Between this zone and the Hastelloy-X is a narrow zone that is depleted in nickel and substantially richer in chromium and molybdenum than Hastelloy-X.

The compatibilities of the 16(Cr)-15(Ni)-6(Mo) and 16-25-6 alloys appear to be quite similar. A typical reaction is shown in Figure 40. The mottled zone was found to be richer in molybdenum and carbon than the unaffected cladding matrix and may consist of very fine molybdenum carbide precipitates.

The reaction with N-155 alloy* was rather irregular and it appeared to be heavier along grain boundaries. This reaction is shown in Figure 41. No microprobe analysis has been undertaken for this alloy.

Inconel 625 (61 w/o Ni), was tested because of its significantly greater strength at elevated temperatures. The same general type of reaction was observed in this material at 700°C as at 800°C. The reaction at 800°C is shown in Figures 42a and 42b. Three separate zones were observed metallographically. One of these was in the direction of the fuel and it appeared to be similar to the zone observed in Hastelloy-X. Beyond the two main reaction zones, precipitates were observed in the cladding. In the case of the 800°C tests, the precipitates gradually became less frequent but larger in size as the distance from the interface increased.

Although the hyperstoichiometric carbide contained approximately 20 w/o (U,Pu)₂C₃, there was no apparent difference in the extent of reaction, compared to single-phase monocarbide, with Inconel 625 at 700°C. At 800°C, however, a somewhat more extensive reaction was observed with the two-phase hyperstoichiometric carbides.

With vanadium-base alloys a more extensive reaction zone was found in V-20w/oTi in contact with the hyperstoichiometric composition than the stoichiometric one at 700°C. In addition to the main reaction zone there appears to be some grain-boundary pene-

TABLE 21. EXTENT OF DIFFUSION ZONES AFTER 42 DAYS (1008 HOURS) OF STOICHIOMETRIC AND HYPERSTOICHIOMETRIC URANIUM-PLUTONIUM CARBIDES WITH POTENTIAL CLADDING MATERIALS (AS DETERMINED BY METALLOGRAPHY)

Material	Temp., °C	Stoichiometric Carbide (4.83 Equivalent w/o C) ^(a) (U _{0.8} Pu _{0.2})C		Hyperstoichiometric Carbide (5.25 Equivalent w/o C) ^(a) (U,Pu)C + (U,Pu) ₂ C ₃	
		Diffusion Zone Width (μ)		Diffusion Zone Width (μ)	
		Average	Maximum	Average	Maximum
Type 304 SS	700	—	—	4	6
	800	Nil	Nil	24	29
Haynes 56	800	Nil	Nil	Nil	Nil
	900	Nil	Nil	Nil	Nil
Hastelloy-X	700	—	—	4	6
	800	8	10	8	11
16-15-6	800	28	34	35	38
16-25-6	800	26	30	32	36
N-155	800	15	37	19	43

^(a) Equivalent w/o Carbon = 0.75 (w/o C + w/o O) + 0.857 (w/o N).

tration into the cladding. The extent of these reactions are shown in Table 24 and in Figure 43. Another couple heat-treated at 800°C, which had previously been examined with a light microscope and had shown a rather irregular reaction zone tending to follow stringers observed in as-received material, was analyzed by means of an electron microprobe. The analysis showed that the darkly-etched phase in the reaction zone and the stringers contain more titanium than the matrix phase. The carbon content of these areas was also found to be slightly higher than that of the matrix.

In contrast, no reaction was seen with the alloy V-15w/oCr-5w/oTi when tested at 800°C. This test was conducted on disks of 30-mil sheet rolled from a small arc-melted button. Further tests will be run when this material becomes available on a larger scale.

h. FUEL-PERFORMANCE STUDIES OF URANIUM-PLUTONIUM CARBIDES

(F. L. BROWN AND L. A. NEIMARK)

Fifteen encapsulated elements containing uranium-plutonium carbides were prepared in a program to characterize the irradiation performance of fuel for LMFBR. Including previously fabricated elements, a total to date of 18 mixed-carbide elements are under-

* An iron-base alloy containing about 1w/oNb, 3 w/o each of Mo and W, and 20 w/o each of Ni and Co. The carbon and nitrogen contents are each about 0.15 w/o.

TABLE 22. EXTENT OF REACTION OBSERVED METALLOGRAPHICALLY BETWEEN (U,Pu) CARBIDES AND INCONEL 625 AFTER 700°C AND 800°C HEAT-TREATMENTS FOR 42 DAYS

Type of (U,Pu) Carbide	Temp. °C	Width of Reaction Zone in Direction of Fuel		Width of Mottled Reaction Zone in Direction of Cladding (μ)		Extent of Precipitates in Cladding Beyond Reaction Zones (μ)	
		Average	Maximum	Average	Maximum	Average	Maximum
Stoichiometric ^(a) and hyperstoichiometric	700	18	30	20	25	25	35
Stoichiometric	800	25	37	23	30	105	135
Hyperstoichiometric	800	36	44	26	36	120	155

^(a) Stoichiometric = 4.83 w/o Equivalent Carbon. Hyperstoichiometric = 5.25 w/o Equivalent Carbon.

TABLE 23. EXTENT OF REACTION OBSERVED METALLOGRAPHICALLY BETWEEN (U,Pu) CARBIDES AND VANADIUM-BASE ALLOYS AFTER 42 DAYS

Type of (U,Pu) Carbide	Alloy, w/o	Temp, °C	Reaction Zone (μ)		Grain-Boundary Penetration (Distance from Interface) (μ)	
			Average	Maximum	Average	Maximum
Stoichiometric	V-20Ti	700	10	35	50	80
Hyperstoichiometric	V-20Ti	700	18	55	65	100
Stoichiometric and Hyperstoichiometric	V-15Cr-5Ti	800	Nil	—	Nil	—

going irradiation in EBR-II for this program. Three mixed-carbide fuel materials and forms are included in the list of 18 elements: (a) vibratorily-compacted columns of physically-mixed powders (UC-20w/o PuC), (b) vibratorily-compacted columns of solid-solution powders ($U_{0.8}Pu_{0.2}$)C, and (c) pressed and sintered pellets of solid solution powders. The fuel-fabrication processes permit adjustment of fuel densities as one variable in the irradiation program. The stoichiometry, with respect to carbon, is stoichiometric or slightly hyperstoichiometric to avoid the questionable effect of a free metal phase in contact with the cladding wall.

Encapsulation of the jacketed elements is necessary to meet EBR-II requirements for irradiation. Sodium is in the annulus between the fuel element and the capsule wall to enhance heat transfer between the outer surface of the jacket wall and the inner surface of the capsule wall. Gas bubbles trapped in the sodium-filled annuli are removed by vibration treatment at 500°C. Elements subsequently are approved for irradiation on the basis of radiography and eddy-current inspection of the annuli.

Design variables include jacketing materials and

43576

500×

Fig. 38. Type 304 Stainless Steel versus Hyperstoichiometric (U,Pu)C 800°C for 42 Days. (10w/o oxalic acid in water.)

jacket wall thicknesses as shown in Table 24. Variations in fuel-column dimensions are insignificant; nominal dimensions are 14 in. length and 0.260 in. effective diameter (jacket ID).

Irradiation variables include heat-generation rate, jacket temperatures, and exposure time or burnup, as shown in Table 24. Values listed in the table are determined by calculation because instrumented capsules cannot be installed in the reactor under present conditions.

Three of the elements, having completed their scheduled exposure, were removed from EBR-II at calculated burnups of 2.1, 2.7, and 3.1 a/o. These elements,

Jacket

Fuel

43636 500×
 FIG. 39. Hastelloy-X versus Hyperstoichiometric (U,Pu)C 800°C for 42 Days. (Orthophosphoric etch.)

43957 500×
 FIG. 41. N-155 (top) versus Stoichiometric (U,Pu)C 800°C for 42 Days. (Orthophosphoric etch.)

43639 500×
 FIG. 40. 16-25-6 (top) versus Stoichiometric (U,Pu)C 800°C for 42 Days. (Orthophosphoric etch.)

jacketed in Types 304 and 316 stainless steel as indicated in Table 24, were examined inside of their irradiation capsules by means of neutron radiography. The radiographs indicate that the jacketing is intact and that the fuel column dimensions are not significantly changed as a result of irradiation. Further examinations, including destructive tests, are scheduled.

Reactor operating conditions and requirements impose certain limitations on the elements within a subassembly. For example, the inability to individually adjust sodium coolant flow for each element, as compensation for the flux variation in the subassembly, results in the wide variation of temperature as indicated in Table 24. Encapsulated elements, as opposed to bare elements, reduce the heat-generation rate required to maintain desired cladding temperatures but thereby increase the exposure time required to attain a burnup objective. A safety analysis was required for the elements in each of the subassemblies listed in Table 24 to assure that operating characteristics would satisfy the EBR-II safety requirements. A safety analysis also was made for the irradiation of a group of elements without capsules in EBR-II. However, the moderate conditions required for unencapsulated experimental fuel elements to fulfill reactor-safety requirements offered no advantages over the continued use of the encapsulated elements.

45378 (Orthophosphoric Etch) 200X 45379 (As-polished) 500X
 FIG. 42. Inconel 625 (top) versus Stoichiometric (U,Pu)C at 800°C for 42 Days.

TABLE 24. SUMMARY OF URANIUM-20 *w/o* PLUTONIUM CARBIDE IRRADIATIONS IN EBR-II

Cladding			Fuel Column			Irradiation			
Composition, <i>w/o</i>	OD, in.	Wall, in.	Material	Form ^(a)	Effective density, %	Power density, kw/ft	Max. clad. temp., °C	Target burnup, <i>a/o</i>	Burnup accumulated as of 12-31-66, <i>a/o</i>
316 SS	0.306	0.024	Physically mixed	Vipac	82	21.7	570	2	2.7 ^(c)
316 SS	0.306	0.024	Solid solution	Pellet	80	16.3	640	2	2.1 ^(c)
304 SS	0.297	0.020	Physically mixed	Vipac	84	19.4	645	5	4.8
Nb-1Zr	0.281	0.012	Solid solution	Pellet	80	15.8	535	6	0.50
Nb-1Zr	0.281	0.012	Physically mixed	Vipac	80	24.3	625	6	0.74
Nb-1Zr	0.281	0.012	Solid solution	Vipac	84	20.0	645	5	5.0
Nb-1Zr	0.281	0.012	Solid solution	Pellet	82	16.7	545	10	3.0
Nb-1Zr	0.281	0.012	Physically mixed	Vipac	80	22.2	605	10	3.9
Nb-1Zr	0.281	0.012	Physically mixed	Vipac	80	25.0	635	10	4.3
Nb-1Zr	0.281	0.012	Solid solution	Vipac	86	24.9	635	10	4.3
Hast.-X	0.297	0.015	Physically mixed	Vipac	80	22.0	670	5	5.0
Hast.-X	0.297	0.015	Physically mixed	Vipac	79	16.6	670	6	0.81
Hast.-X	0.297	0.015	Physically mixed	Vipac	80	22.7	640	10	3.8
Hast.-X	0.297	0.015	Physically mixed	Vipac	80	25.0	670	10	4.2
Hast.-X + W ^(b)	0.297	0.020	Solid solution	Pellet	82	16.1	555	10	2.9
Hast.-X + W ^(b)	0.297	0.020	Solid solution	Vipac	83	24.6	685	10	4.3
Vanadium	0.301	0.022	Solid solution	Vipac	86	25.5	640	2	3.1 ^(c)
V-20Ti	0.297	0.020	Solid solution	Vipac	82	21.4	620	6	0.65

^(a) Vipac indicates vibratory compacted powders.

^(b) 0.38 mm Hastelloy-X with 0.13 mm of vapor-deposited tungsten on the ID.

^(c) Burnup at time of discharge.

TABLE 25 SUMMARY OF VIBRATORILY-COMPACTED CARBIDE IRRADIATIONS

Specimen Number	Fuel	Jacket Material	w/o C in PuC	Burnup		Max Jacket Surface Temp, °C	Maximum % Δ Dia	% ΔL	% ΔV	Gas Release, % Theoretical
				a/o	I fss/cc $\times 10^{20}$					
F-7	PuC	304 SS	4.24	2.0	5.1	495	1.0	0.1	1.1	35.2
F-6	PuC	304 SS	6.22	5.4	13.1	625	0.8	Specimen Melted Jacket Ruptured		
F-8	PuC	304 SS	4.24	6.0	16.0	675	14.3			
C-44	PuC	Nb-1Zr	3.40	2.2	5.3	625	0.5	Neg	0.3	45.9
C-43	PuC	Nb-1Zr	4.24	5.3	14.0	550	0.1	Neg	0.3	31
F-18	UC-20PuC	304 SS	6.42	1.4	3.4	505	0.3	Neg	0.6	8.8
F-21	UC-20PuC	304 SS	3.40	1.4	3.5	430	0.5	Neg	0.2	25.7
F-19	UC-20PuC	304 SS	6.22	5.0	12.9	570	2.8	0.3	3.5	<1
F-20	UC-20PuC	304 SS	4.24	6.0	16.0	645	4.7	1.3	7.3	40
C-69	UC-20PuC	Nb-1Zr	6.42	1.2	3.1	405	0.5	Neg	0.3	5.7
C-74	UC-20PuC	Nb-1Zr	3.40	1.6	4.1	455	0.3	Neg	0.5	21.5
C-72	UC-20PuC	Nb-1Zr	6.22	5.8	15.4	635	0.2	Neg	0.4	<1
C-70	UC-20PuC	Nb-1Zr	4.24	6.9	19.3	650	0.4	Neg	0.5	20

**i. IRRADIATION BEHAVIOR OF
VIBRATORILY-COMPACTED UC-20w/oPuC
POWDERS** (Y. K. YOON, L. A. NEIMARK
AND H. WATANABE*)

The irradiation behavior of uranium and plutonium carbide specimens is being studied with use of instrumented temperature-controlled capsules in the MTR and CP-5 reactors. The specimens studied are physical mixture fuel and solid-solution material both vibratorily-compacted pellet fuel. The objectives of this irradiation program are (1) to investigate the irradiation behavior of carbide fuel with respect to swelling, fission-gas release, micro- and macrostructural changes, and jacketing compatibility, and (2) to develop information needed for the performance evaluation of carbide prototype fuel elements for the LMFBR materials program. The initial emphasis has been on vibratorily-compacted physical mixtures of UC-20w/oPuC powders. Irradiations have been completed on vibratorily-compacted specimens at the nominal 2 and 5 a/o burnup levels at 600°C. Specimens for the 10 a/o level at 600°C and 800°C are still in the MTR.

Postirradiation examination was conducted on the vibratorily-compacted UC-20w/oPuC specimens that were irradiated in the MTR to a maximum analyzed burnup of 6.9 a/o of the heavy atoms (1.8×10^{21} fss/cc) ^(17,18). This corresponds to a burnup of 34%

45932

500×

FIG. 43 Vanadium-20w/o Titanium (top) vs Stoichiometric (U,Pu)C 700°C for 42 Days (Etched with 5% AgNO₃ + 2% HF in water)

in the PuC phase, since the uranium was not enriched. The specimens were jacketed either with 0.23 mm (0.009 inch) thick Type 304 stainless steel or Nb-

Irradiation of Uranium and Plutonium Carbide Fuels, ANL-7155, p. 84 (1965)

* Now at Japan Atomic Energy Research Institute, Tokai, Japan

⁽¹⁷⁾ Ayer, J. E., Soppet, F. E., Talaber, G. F., and Bieler, B. H., *Production of PuC and (U,Pu)C and Fabrication of Carbide Fuel Elements*, pp. 29-33 in ANL-7155 (1966)

⁽¹⁸⁾ Neimark, L. A., Reinke, C. F., and Crothers, C. C.,

EI-4652

38×

FIG. 44. Continuous Areas of $\text{PuC}_{1.33}$ Surrounding Large Particles of UC.

1w/oZr with an outer diameter of 4.42 mm (0.174 in.). The PuC fraction, 74 to 125 microns (120 to 200 mesh) in size, contained 4.24 w/o carbon in some specimens and 6.22 w/o carbon in others. The carbon content of the UC fraction, 420 to 841 microns (20 to 40 mesh) and smaller than 44 microns (~ 325 mesh) in size, was approximately 4.8 w/o but on both sides of the stoichiometric composition.

The specimens operated at maximum jacket-surface temperatures ranging from 570° to 650°C. Table 25 shows irradiation data and results of the postirradiation dimensional measurements reported previously.⁽¹⁸⁾ Previous burnup values estimated from heat-generation rates have been updated with analyzed values. Dimensional changes on the specimens jacketed with Nb-1w/oZr were negligible while the specimens jacketed with stainless steel had diametral increases up to 4.7% and volume increases up to 7.3%. Fission-gas release was dependent on the carbon content of PuC, with the hypostoichiometric (UC-PuC_{1-x}) fuel releasing up to 40% of the amount produced compared to less than 1% for the hyperstoichiometric (UC-PuC_{1+x}) fuel. Only slight reaction occurs between the PuC and jacketing of either stainless steel or Nb-

EI-4783

250×

FIG. 45. $\text{PuC}_{1.33}$ Swelled into Void Between UC Particles.

EI 4800

183×

FIG 46(a) Interconnected Large Fission Gas Bubbles in $\text{PuC}_{0.89}$

EI 4852

183×

FIG 46(b) Sintered $\text{PuC}_{1.33}$ with Trapped UC Particles and Fission Gas Bubbles

1w/oZr. Maximum inner jacket temperatures were about 700°C.

The metallographic examination of all specimens showed that extensive sintering and swelling of the PuC had occurred. The PuC phase formed an almost continuous network around the coarse UC particles as shown in Figure 44. The fine UC particles were found

trapped between swelled particles of PuC. The apparent growth of the PuC areas can be attributed to swelling and to a lesser extent to reaction-sintering with the fine UC particles. Figure 45 shows the swelling of PuC_{1+x} into a void area between two large UC particles. The PuC_{1+x} appears to be very plastic as it swelled as indicated by its adherence to the contour

EI 4913

FIG 47 White Phase at Edge of $\text{PuC}_{1.33}$ Fueled Specimen

250×

EI-4799

175×

FIG 48 Areas Depleted in Higher Carbides in UC Particles

of the UC particles and the convex nature of its frontal surfaces. The PuC_{1+x} was less plastic than the PuC_{1-x} as evidenced by the relative size of the trapped fission gas bubbles.

The fission gas bubbles in the PuC_{1-x} were generally larger and more interconnected than those in the PuC_{1+x} . This gave rise to the greater fission gas release by a factor of about ten in the PuC_{1-x} specimens. Figures 46(a) and 46(b) show the fission gas bubbles near the center of a PuC_{1-x} and a PuC_{1+x} fueled specimen, respectively. The gas bubbles near the outer edge of the specimens were considerably larger than in the interior in all specimens. The burnup is higher at the outer edge on account of the flux perturbation in a thermal reactor.

The PuC fraction in all specimens had varying degrees of a white phase primarily in the cooler regions and to a larger extent around gas bubbles. Figure 47 shows this phase in a $\text{PuC}_{1.33}$ specimen. Since the individual PuC particles achieved burnups of approximately 29%, this phase is probably a solid fission product, although no positive identification has yet been made. This was the only structural feature of the PuC that was discernible with optical microscopy.

Figure 48 shows a structural alteration in the UC_{1+x} particles. The UC_2 platelets, originally in a Widmanstätten structure, were depleted at the surface of the UC particles and adjacent to internal cracks. The depletion next to cracks is an indication that at least part of the loss occurred by a gas-phase reaction rather

106-9245

FIG. 49. Comparison of Fission-Gas Bubble-Size Distributions in $\text{PuC}_{1.33}$ and $\text{PuC}_{0.89}$.

than the solid solution formation across the UC-PuC phase boundaries.

Finer microstructural features could not be observed under the optical microscope. Frequently, fission product particles were taken for small fission gas bubbles. Hence, electron microscopic studies are being conducted on several high burnup specimens by the two-stage carbon-replica method.⁽¹⁹⁾ The specimens were

⁽¹⁹⁾ Yoon, Y. K., Watanabe, H., and Kittel, J. H., *Electron Microscopic Studies of Structural Changes in High Burnup*

121195

FIG. 50. Fission Gas Bubbles and Second Phase Particles in $\text{PuC}_{1.33}$ Irradiated to 29 a/o Burnup (1.52×10^{21} fissions/cc).

121197

FIG. 51. Second Phase Particles of Various Sizes in $\text{PuC}_{1.33}$ Irradiated to 29 a/o Burnup (1.52×10^{21} fissions/cc).

ground and polished in the usual manner for optical metallography.

Replication was done on chemically-etched surfaces by using an acetyl cellulose film moistened in acetone. After decontamination, the plastic replicas were shadowed with Pt-20%Pd alloy and deposited with carbon. The plastic film was dissolved away and the carbon replicas were examined in the electron microscope.

In the electron micrographs, small bubbles were clearly distinguished from second-phase particles with diameters generally less than one micron. The size distributions of fission-gas bubbles in PuC_{1-x} and in PuC_{1+x} , determined in both cases, by use of both optical and electron micrographs, are compared in

UC-PuC, presented at IAEA Symposium, Brussels, March 13-17, 1967.

121209

FIG. 52. Interface between UC_{1+x} and PuC Particles.

Figure 49. Spherically-shaped second-phase particles of several sizes were observed in the PuC_{1+x} as shown in Figures 50 and 51. Larger particles have black fringers, and finer particles tend to segregate. They appear to be of different origin or composition. There were also irregularly-shaped particles inside or on the edges of small bubbles. These second-phase particles are assumed to be associated with solid fission products in the PuC.

The depletion of UC_2 platelets near the surface of the UC particles was similarly observed in electron micrographs as shown in Figure 52. Also shown in the electron micrograph were many fine globular particles that were not found in the PuC particles. Figure 53 shows these globular particles and UC_2 platelets in a high magnification. Electron microscopic studies are being continued on the hypostoichiometric specimen.

Use of a shielded microprobe to be installed during

121226

FIG. 53. UC_2 Platelets and Second Phase Particles in UC_{1+x} .

1967 should facilitate identification of the various solid fission-product phases, and aid in establishing whether or not any solid-solution formation occurred across the UC-PuC phase boundaries. The second-phase particles are believed to affect the distribution of fission gas bubbles. This distribution, in turn, is known to influence fuel swelling and fission-gas release. Further studies by use of electron microscopy and microprobe analysis are warranted to obtain a better understanding of the irradiation behavior of various fuel materials.

The information so far obtained substantiates the belief that the initial porosity can accommodate fuel swelling, if sufficient jacket restraint is present.⁽²⁰⁾ Irradiation experiments with specimens of solid-solution pellet fuel are planned.

⁽²⁰⁾ Neimark, L. A., *The Irradiation Behavior of Vibratorily-Compacted UC-20w/oPuC Powders*, ANS Trans., **9**, 415 (1966).

4. Development of Doppler-Element Loading Techniques (J. E. AYER)

Thirty-two capsules containing plutonium oxides were fabricated for doppler effect experiments. The capsules were made of glass-bonded pellets. The glass-bonding requirement was one approach to meeting the specification that the fuel body be made up of low-density, cored, pellets. These bodies were constrained during the physics experiment to prohibit axial growth upon heating. Discussions with the experimentalists revealed that all necessary conditions may be met by columns of particles.

Columns of particles might be more easily con-

strained during the heating cycle. This judgment was based upon the following: A column of particles, after sufficient vibration, is self-supporting and somewhat rigid due to interlocking of granules. If such a column is constrained axially and heated the granules will expand and the resultant forces on particles will cause fragmentation. Fragments split from parent particles will move to voids and channels within the matrix thus relieving the stress upon the localized area. In this manner a gradual and continuing relief is accomplished by modest constraining force.

TABLE 26. PERFORMANCE AND CONTENT OF GRANULAR DOPPLER SPECIMENS

Capsule Number	Specimen Charge				
	Composition	Source	Size ^(a)	Weight ^(b)	
N-12	Nat'l. UO_2	Crushed pellets	14/25	983.7	Unsatisfactory-excessive void
N-13	Nat'l. UO_2	Crushed pellets	25/50	946.6	Satisfactory
N-14	Nat'l. UO_2	Crushed pellets	50/100	877.5	Excellent
HE-5	Enriched UO_2	Fired granules	50/100	813.7	Excellent
N-15	Nat'l. UO_2	Powder	-325	589.5	—

^(a) All sizes are U.S. Sieve Series.

^(b) All weights are Grams.

350-895

FIG. 54. Doppler Effect Test Element and Components.

In the event that the above analysis is correct one can expect granular columns to be more advantageous than pellet columns. The pelleting route previously taken required fired granules as a matrix that was held together by sodium silicate. The mixture of granules and "water glass" was then pressed into core pellets, which were fired, measured for diameter and length, weighed, and loaded. The direct loading of granules would obviate all pelleting and subsequent mensuration.

In order to test the adequacy of granular columns in the doppler experimentation a series of five capsules were loaded with various granular materials. Each capsule was radiographed then subjected to the heating cycle while the neutron spectrum was monitored for comparison against existing controls. Table 26 shows the results of this work.

The performance of the 50/100 mesh granules, derived from either crushed pellets or fired granules, supported the original premise that constraint could be easily impressed on columns of grains. Figure 54 is an exploded view of a nonexpandable doppler cap-

sule. The object of the bellows on either end is to allow the restraint of the column along its axis. This particular configuration permitted another dividend in fabrication. Work on vibratory compaction has revealed that columns of particles may be disturbed and "unpacked." Armed with this knowledge the capsule designated as HE-5 in Table 26 was returned to fabrication where the pistons were drawn back and the column was subjected to vibration and repacking without breaching the leak tight integrity of the capsule. This particular capsule has been "revitalized" twice at this time and has been found to perform satisfactorily after each regeneration. The ability to regenerate the fuel column relieves fabrication of many hours of work.

The development described above preceded a request for the Plutonium Fabrication Group to manufacture 28 doppler elements of $\frac{1}{2}$ inch and 1-inch nominal diameter. During this calendar year equipment to carry out the fabrication was designed or procured and the process was fixed. At present two 1-inch diameter non-expandable elements have been loaded and are ready for closure.

5. Fast-Reactor Jacket Development

a. IMPROVEMENTS IN CONSOLIDATION AND FABRICATION OF V-15w/oTi-7.5w/oCr

W. R. BURT, JR., W. C. KRAMER, F. J. KARASEK,
J. E. FLINN, AND R. M. MAYFIELD)

Since the detailed report on the consolidation and fabrication of V-15w/oTi-7.5w/oCr was published⁽²¹⁾ certain improvements in the processing of this alloy have been made. These improvements are described herein along with brief mention of existing practice to provide continuity of experimental details and results.

(1) Consolidation

The consolidation procedure originally established⁽²²⁾ has been modified but little. The charge materials—vanadium chips (granules), titanium sponge and chromium flakes—are weighed on the basis of V-15w/oTi-7.5w/oCr and compacted into rectangular or cylindrical briquets. The briquets are heated in vacuum to drive off the die lubricant (stearic acid) and then welded together to form consumable electrodes. Formerly, a long continuous weld was made down both sides of the electrode to increase strength and decrease electrode resistance. This welding operation has since been eliminated to both simplify the process and to avoid possible oxygen contamination.

Two electrodes (12 to 14 briquets each) are used to make a single 2.5 in. diameter by ~10 in. long arc-cast ingot. Three of these cast ingots are welded together to form the electrode for remelting into the final 3.8 in. diameter ingot. All arc melts are made under straight-polarity (consumable electrode negative) conditions. First melts of briquet electrodes were performed at a power setting of ~75 kw (50 volts and 1500 amperes) and a stirring coil setting of 1.5 amperes. Melt rates were 0.9 to 1.1 lb/min. Remelting required ~113 kw (42 volts and 2700 amperes) with 3 amperes on the stirring coil. The remelt rate was 2.2 lb/min. An inert atmosphere consisting of 75 v/o (volume percent) helium and 25 v/o argon at approximately 500 torr was used for all melting operations. No charge weight was lost during either of the melting operations.

To date, five arc-cast production ingots have been produced by the above described consolidation tech-

niques. Each cropped ingot weighed between 28 and 30 lbs. Analytical results on the five ingots are given in Table 27. AM-94 was consolidated from less pure raw material (vanadium) than the previous ingots and the total interstitial content is correspondingly higher. High-purity vanadium is in short supply. Accordingly, remaining vanadium stocks have been carefully classified as to purity in an effort to control the interstitial content in the charge material at or near previously prescribed levels.

(2) Primary Fabrication

The procedure employed for primary fabrication of the V-15w/oTi-7.5w/oCr consists of a low ratio breakdown extrusion of the ingot into bar stock followed by a re-extrusion into rod, sheet-bar and tube-blanks suitable for secondary fabrication.

Conditioned ingots (billets) are canned in Type 304 stainless steel, heated for a minimum of two hours in a conventional air atmosphere furnace and extruded on a 1250 ton horizontal press. The nominal 3.7:1 reduction ration yields a solid bar approximately 2.1 in. in diameter. The stainless steel jacket and striated surface of the alloy are removed in machining the bar stock into suitable re-extrusion billets. The machined billets are again canned in 304 stainless steel and extruded on a 350 ton vertical press into rod, sheet-bar and tube-blanks. Re-extrusion temperatures range from 1100 to 1150°C with reduction ratios of up to 13:1 for sheet-bar.

After re-extrusion, the products are straightened and the protective stainless steel jacket removed. On rods, sheet-bar, and the outer surface of tube-blanks the jacket is removed by mechanical peeling. The jacket is removed from the internal surface of tube-blanks by pickling. After dejacketing, extruded tube-blanks are approximately 0.875 in. OD by 0.635 in. ID. The length varies as a function of the original billet length and of the reduction ratio, most tube-blanks being about 40 in. long.

(3) Secondary Fabrication

(a) Rod and Sheet

Conversion of extruded rod and sheet-bar into finished product is accomplished by cold-rolling. The dimensions of the dejacketed product are approximately 0.580 in. diameter for rod stock and approximately 0.22 in. thick by 1.00 in. wide for the sheet-bar. The final products are typically ~0.30 in. diameter for rod stock and 0.060 in. thickness for sheet.

⁽²¹⁾ Kramer, W. C., Burt, W. R., Jr., Karasek, F. J., Flinn, J. E., and Mayfield, R. M., *Vanadium Alloy Screening Studies and Fabrication of V-15w/oTi-7.5w/oCr Tubing for Nuclear Fuel Cladding*, ANL-7206 (August 1966).

⁽²²⁾ *Annual Progress Report for 1965, Metallurgy Division*, ANL-7155, p. 45.

Unlike the V-20w/oTi alloy, which was easily cold-rolled from the as-extruded condition,^(23,24) the V-15w/oTi-7.5w/oCr ternary alloy requires a 900°C anneal after extrusion. The alloy can be easily cold-rolled to final sizes. In-process anneals—1 hr at 900°C—are required after ~60 percent reduction in area.

(b) Tubing

The secondary fabrication operations have been refined considerably during the year by the use of three roll tube-reducers designed and built at ANL. The reducer (Figure 55) processes the swaged and lightly conditioned tube-blank from 0.800 in. OD by 0.600 in. ID to ~0.375 in. OD by 0.335 in. ID according to the pass schedule shown in Table 28. The tube-reducing operation significantly reduces the number of processing steps from extruded tube-blank to finished tubing. It also circumvents many of the worrisome problems of drawing such as uniform deformation, lubrication, tooling, etc. The tube-reduced product is mandrel drawn a few passes and then plug drawn for final size. A chlorinated wax-type lubricant over a plastic base coat permits the use of standard carbide tooling.

A sufficient quantity of vanadium-base alloy tubing has now been processed to firmly establish the flow chart of Figure 56. Yields have been high—values of >90 percent (weight of starting tube-blank to finished drawn tubing) are typical.

(4) Commercial Fabrication of V-15w/oTi-7.5w/oCr Alloy Tubing

To date, industrial participation in the fabrication of the V-15w/oTi-7.5w/oCr alloy has been limited to a single order for redraw of tube-blanks. The Superior Tube Company, Norristown, Pennsylvania, converted nine tube-blanks produced at ANL into finished tubing measuring 0.220 in. OD by 0.016 in. wall thickness.

The vendor indicated no difficulty in processing the tubing. Upon receipt at ANL the tubing was inspected by a pulsed eddy current technique. Only one small defect (>10 percent of the wall thickness and about 1 in. long) was found in 216 feet of tubing.

(5) Annealing Behavior of V-15w/oTi-7.5w/oCr

A comprehensive annealing study of the ternary alloy is under way but incomplete at the close of the

TABLE 27. ANALYTICAL RESULTS ON FIVE PRODUCTION-SIZE ARC-CAST V-15w/oTi-7.5w/oCr ALLOY INGOTS

Ingot Number	Alloy Content, w/o ^(a)		Interstitial Content, ppm ^(b)				Total Interstitial Content
	Titanium	Chromium	Carbon	Oxygen	Nitrogen	Hydrogen	
AM-64	14.8	7.5	250	700	400	14	1364
AM-68	14.7	7.3	225	810	415	15	1465
AM-75	14.9	7.6	235	645	460	35	1375
AM-92	15.0	7.3	225	570	270	8	1073
AM-94	14.9	7.3	340	935	375	30	1680

^(a) Average of three values from top, center and bottom of ingot.

^(b) Average of two values from top and bottom of ingot.

reporting period. Results of an earlier preliminary annealing study are reported in ANL-7206.⁽²¹⁾

The hardness resulting from various reductions in area (at room temperature) is shown in Figure 57 for both V-20w/oTi (AM-82) and V-15w/oTi-7.5w/oCr (AM-75) alloys.

Both alloys were given a recrystallization anneal after extrusion, cold-rolled to 0.5 in. diameter rod, again annealed and rolled to 0.4 in. diameter rod. Before further cold-rolling to specific reductions both materials were annealed at 900°C for one hour. Studies on similar materials reduced 35 and 70 percent and subjected to temperatures ranging from 600 to 1500°C for times from 15 to 360 minutes are in progress.

B. ALLOY DEVELOPMENT (VANADIUM-BASE ALLOYS) (F. J. KARASEK AND R. M. MAYFIELD)

Interest in the V-10w/oCr binary and V-15w/oCr-5w/oTi ternary alloys has prompted a scale-up from arc button melts to larger ingots in order to provide the material needed for (1) a more definitive evaluation of fabrication parameters for rod, sheet and tubing, and (2) a comprehensive testing program on finished (wrought) products.

The secondary fabrication of both of these alloys is expected, on the basis of early evaluation studies,⁽²⁵⁾ to be more difficult than that of the 7.5w/oCr ternary alloy. The V-15w/oCr-5w/oTi alloy was rated as "considerably more difficult" to fabricate than V-20w/oTi. The V-10w/oCr was similarly classified. Accordingly, before any scale-up of these alloys was seriously considered, a fabricability re-evaluation was conducted on arc-melted button stock of each alloy. As with the 7.5w/oCr ternary alloy, a heat-treatment after hot-breakdown seemed to improve subsequent fabrication by cold-rolling. On this premise, the pros-

⁽²³⁾ Burt, W. R., Jr., Kramer, W. C., McGowan, R. D., Karasek, F. J., and Mayfield, R. M., *Consolidation and Fabrication Techniques for Vanadium-20w/oTitanium (TV-20)*, L-6928, (February 1965).

⁽²⁴⁾ Burt, W. R., Jr., Kramer, W. C., Karasek, F. J., and Mayfield, R. M., *Improvements in Consolidation and Fabrication of Vanadium-20w/oTitanium (TV-20)*, ANL-7127 (May 1966).

⁽²⁵⁾ *Annual Progress Report for 1965, Metallurgy Division*, ANL-7155, p. 40.

106-9184

FIG. 55. Overall View of ANL Three-Roll Tube-Reducer (Including Tubing Feed and Index Mechanism).

TABLE 28. ANL TUBE REDUCTION DATA FOR
V-15w/oTi-7.5w/oCr TUBE BLANKS^(a)
(Starting Size ~0.800 in. OD by 0.600 in. ID by 38 to 44 in. Long)

Three-Roll Reducer Pass Schedule ^(b)	Reducer Roll Diameter	Mandrel Diameter	Reduced Tube Size		Approximate Percent Reduction		Final d/t
			OD	ID	Area	Wall	
1	0.875 → 0.750	0.581	0.766	0.581	11	8	8.3:1
2 ^(c)	0.750 → 0.625	0.500	0.637	0.500	38	26	9.3:1
3	0.625 → 0.562	0.484	0.567	0.484	44	39	13.6:1
4 ^(c)	0.562 → 0.500	0.437	0.502	0.437	30	22	15.4:1
5	0.500 → 0.437	0.387	0.442	0.387	25	15	16:1
6	0.437 → 0.375	0.335	0.382	0.335	26	15	16.2:1

^(a) All dimensions are in inches.^(b) Roll changes are accomplished in five to ten minutes.^(c) Intermediate anneals usually scheduled after the second and fourth passes.

pects for producing high-quality finished tubing from these alloys appeared good—but not guaranteed. Within these limits, an initial scale-up of the two alloys was scheduled.

FIG. 56. Partial Fabrication Flow Chart for Vanadium-Base Alloy Tubing (all Dimensions in Inches).

Recalcitrant materials can often be processed into finished sheet and rod stock by a variety of expeditious means. The processing can involve warm working operations to near the final stages of reduction. When such practices could be applied to tubing, it is the intention of this program to develop both a practical and economic technology—one that could be immedi-

FIG. 57. Hardness as a Function of Percent Reduction of Area by Cold-Rolling for V-20w/oTi and V-15w/oTi-7.5w/oCr Alloys.

ately utilized by industry, if the need arose. Warm drawing is outside the immediate scope of this objective.

(1) Initial Scale-Up Studies

(a) Consolidation

Fifteen-pound semi-production ingots of both alloys (V-10w/oCr and V-15w/oCr-5w/oTi) have been successfully consolidated by use of briquet compaction techniques and a double consumable arc melting practice similar to that used for the 7.5w/oCr ternary alloy. Ingot chemistry for both of the presently considered alloys is shown in Table 29.

(b) Primary Fabrication

The arc-cast 3.8-inch diameter ingots were inspected, cropped machined and ingots of both alloys extruded in the same mild steel can at 1100°C and a reduction ratio of 3.7:1. Three billets were machined from the extruded bar stock of each alloy. After being canned in Type 304 stainless, the billets were re-extruded into a rod, into sheet-bar and into a tube-blank. Extrusion data for both alloys is shown in Table 30.

(c) Secondary Fabrication

A fabricability evaluation of the re-extruded products was incomplete at the close of the reporting period.

Certain thermal treatments will permit cold rolling of 0.2 in. thick sections of sheet-bar while failing to produce a cold-workable structure in the 0.5 in. diameter extruded rod stock. The sheet-bar has a more homogeneous microstructure than the rod stock, probably because of a higher extrusion temperature and reduction ratio (Table 30). This structural difference tends to confirm the noted fabricability variations,

TABLE 29. CHEMICAL ANALYSES ON V-15w/oCr-5w/oTi AND V-10w/oCr SEMI-PRODUCTION INGOTS

Ingot Number and Composition	Alloy Content, w/o ^(a)		Interstitial Content ^(b) , ppm				Total Interstitials
	Chromium	Titanium	Carbon	Oxygen	Nitrogen	Hydrogen	
AM-97 V-15w/oCr-5w/oTi	14.4	5.5	280	900	250	13	1443
AM-99 V-10w/oCr	10.2	—	310	705	280	22	1317

^(a) Average of three values from top, center and bottom of ingot.

^(b) Average of two values from top and bottom of ingot.

but additional information will be required before optimum extrusion parameters can be specified.

A range of thermal treatments is being investigated and the effects upon microstructure, hardness and fabricability are being determined. A double thermal treatment of the type proposed by Perkins and Lytton⁽²⁶⁾ in processing a dispersion-strengthened Mo-1.5w/oCb-0.5w/oTi-0.3w/oZr-0.08w/oC alloy will be investigated—it may prove useful in the processing of certain vanadium alloys.

The effects of a 1200°C thermal treatment upon the microstructure and hardness of extruded sheet-bar of both alloys are shown in Figures 58 and 59. The thermal treatment has a mitigatory effect upon the stringers that are clearly evident in the as-extruded structure of the 15w/oCr ternary alloy (Figure 58). The grain size has been effected remarkably little by the treatment while evidence of banding has been emphasized. In contrast, the V-10w/oCr alloy (Figure 59) exhibits little resistance to grain growth and the banding, noted in the as-extruded structure, is largely eliminated by the 1200°C treatment.

c. CORROSION OF JACKET MATERIALS FOR SODIUM-COOLED REACTORS (H. A. LEVIN AND J. W. SCHLAMER)

The program to determine the reaction mechanism of V-20w/oTi in sodium containing low concentrations of oxygen has continued. V-20Ti was exposed to sodium containing 1 to 6 wt. ppm oxygen over the temperature range of 550 to 750°C for times up to 475 hours. An effective sodium velocity of 2.45 cm/sec was maintained by rotation of the sample cage. The specimens

⁽²⁶⁾ Perkins, R. A., and Lytton, J. L., *Effect of Processing Variables on the Structure and Properties of Refractory Alloys*, AFML-TR-65-234, Part I (July 1965). Lockheed Missiles and Space Company.

TABLE 30. EXTRUSION DATA ON V-15w/oCr-5w/oTi AND V-10w/oCr FOR BREAKDOWN AND RE-EXTRUSION

Extrusion Number and Alloy	Extrusion Product	Billet Temperature °C	Reduction Ratio	Extrusion Speed in./sec	Extrusion Pressure		Extrusion Constant <i>K</i> psi
					Break-through psi	Running psi	
638 (ingot breakdown—two ingots in same can) V-15w/oCr-5w/oTi V-10w/oCr	Bar	1100	3.75	3.00	121,000	111,000	84,000
	Bar	1100	3.75	3.00	93,000	80,000	60,000
639 V-15w/oCr-5w/oTi Re-extrusion	Rod	1100	10.6	4.25	164,000	157,000	66,500
640 V-10w/oCr Re-extrusion	Rod	1000	10.6	5.5	134,000	127,000	53,700
641 V-15w/oCr-5w/oTi Re-extrusion	Sheet-Bar	1150	13	4.5	162,000	153,000	59,600
642 V-10w/oCr Re-extrusion	Sheet-Bar	1050	13	5.0	130,000	125,000	48,750
643 V-15w/oCr-5w/oTi Re-extrusion	Tube Blank	1100	8	4.5	142,000	133,000	64,100
644 V-10w/oCr Re-extrusion ^(a)	Tube Blank	935	8	5	138,000	—	—

(a) Billet stalled. Pressure figure for section that did extrude.

gained weight in this range of conditions and the process initially followed a parabolic rate law, $\Delta w^2 = K_p t$. Any subsequent deviations from parabolic behavior were in the direction of lower weight gains.

The data are summarized in Table 31. It is quite apparent that the parabolic rate constant depended to a large extent on the oxygen level in the sodium. To approximate the behavior of the alloy in "hot-gettered" sodium (1–6 wt. ppm oxygen), the average value of the rate constant at each temperature is plotted as a function of temperature (Figure 60), resulting in an activation energy of 22.8 Kcal/mole.

A photomicrograph of a sample exposed to sodium containing 6 wt. ppm oxygen for 40 hours at 650°C is shown in Figure 61. The appearance is typical for all of the exposed V-20Ti samples exposed to low oxygen sodium. No surface oxide is present on the specimens. The observed weight gains are the result of the solution of oxygen in the alloy rather than the formation and growth of a protective oxide film.*

* The behavior of sodium-exposed samples in nitric-hydrofluoric acid solution may be of interest. A nonuniform rate of removal of the oxygen-rich zone results upon etching (i.e.

The solution of oxygen at the surface results in an oxygen concentration gradient and inward diffusion of oxygen. Oxygen enters the lattice interstitially causing solid solution hardening. The extent of this hardening is graphically illustrated in Figure 61 by the decrease in size of the Knoop microhardness indentations (15 gm load) as the surface is approached.

Microhardness profiles taken from samples exposed under various conditions are shown in Figure 62. The large variation in the extrapolated surface hardness is significant. In general, at any given temperature of exposure, the higher the surface hardness (i.e. oxygen concentration), the larger the parabolic rate constant and (for a given temperature and time of exposure) the thicker the diffusion zone.

In sodium containing less than approximately 10 wt. ppm oxygen, V-20Ti gains weight by solution and diffusion of oxygen into the metal rather than through the formation and growth of a protective oxide film. This mechanism is consistent with the observed pa-

thin plates of material are removed). Unexposed material dissolves uniformly. This phenomenon points up the need for precision in use of descriptions such as film.

Hardness (As Extruded at 1100°C): 222 DPH (10 kg Load)

46176

150×

46178

1000×

After 1200°C—One Hour Hardness: 198 DPH (10 kg Load)

46179

150×

46180

1000×

FIG. 58. Microstructures of V-15w/oCr-5w/oTi Alloy Sheet-Bar before and after 1200°C—One Hour Thermal Treatment.

bolic kinetics. For the case of solution and diffusion of oxygen into the metal for our sample geometry (a thin flat plate) provided the oxygen does not diffuse to the center of the sample, the samples would be expected to gain weight according to the following relationship:

$$\left(\frac{\Delta w}{A}\right)^2 = A_n(C_s - C_o)^2 Dt$$

where the rate constant $K_p = A_n(C_s - C_o)^2 D$ and A_n is a numerical constant, C_s is the surface concentration of oxygen, and C_o is the original concentration of oxygen in the metal.

According to the above expression, increasing the concentration of oxygen in the solid at the surface should result in an increased rate constant. An increase

in the rate constant with an increase in surface hardness has been observed. The increase in surface hardness (surface concentration of oxygen) is a direct result of an increase in the oxygen concentration of the sodium. In the range of surface hardnesses found, the variation of hardness with oxygen concentration is not quantitatively known. Therefore, quantitative verification of the above dependence of the rate constant on the surface concentration cannot be accomplished.

At a fixed oxygen level in the sodium and for $C_s \gg C_o$ the temperature dependence of the rate constant is as follows:

$$\frac{d \ln K_p}{d(1/T)} = \frac{2d \ln C_s}{d(1/T)} \frac{\Delta H_{\text{diff.}}}{R}$$

Hardness (As Extruded at 1050°C): 251 DPH (10 kg Load)

46181

150×

46183

1000×

After 1200°C—One Hour Hardness: 240 DPH (10 kg Load)

46184

150×

46185

1000×

FIG. 59. Microstructures of V-10w/oCr Alloy Sheet-Bar before and after 1200°C—One Hour Thermal Treatment.

TABLE 31. EXPOSURE OF V-20Ti IN SODIUM OF LOW OXYGEN CONCENTRATION (HOT-GETTERED)

Temperature, °C	Length of Exposure, Hours	Rate Constant, $K_p(\text{mg}^2/\text{cm}^2 \text{ hr}^{-1})$	Surface Hardness ^(a) , KHN (15 g Load)	Oxygen Content in Na, wt ppm
550	85	3.8×10^{-4}		
550	475	1.5×10^{-4}	2600	
600	32	4.9×10^{-4}	1300	1.2
650	333	2.7×10^{-4}	1600	
650	32	6.2×10^{-4}	1500	3.8
650	32	18.8×10^{-4}	1950	4.5
650	40	30.0×10^{-4}	2600	6.3
700	32	5.2×10^{-4}	700	2.3
700	32	13.2×10^{-4}	800	2.3
750	32	17.0×10^{-4}	1000	4.6
750	32	43.0×10^{-4}	2000	4.4

^(a) Extrapolated value—see Figure 60.

This expression is the difference of the activation energy for diffusion of oxygen in the alloy from the rate of change of the surface concentration with temperature. Depending on the thermodynamics of the system, $d \ln C_s/d (1/T)$ can be positive or negative. In the absence of thermodynamic and diffusion data for the V-Ti system, the relative effect of each quantity on the observed activation energy of 22.8 Kcal/mole cannot be determined.

d. DEVELOPMENT OF REFRACTORY-METAL ALLOYS FOR SERVICE IN OXYGEN-CONTAMINATED SODIUM (W. E. RUTHER AND D. J. DORMAN)

Publication

Greenberg, S., Ruther, W. E., and Levin, H. A., *Corrosion of Vanadium-Base Alloys in Sodium at*

550°C to 750°C. Presented at IAEA Symposium on Alkali Metal Coolants—Corrosion Studies System Operating Experience, Nov.–Dec., 1966. (To be published by IAEA, 1967.)

The interest in refractory-metal alloys was initially based on the need for fast reactor jacket materials compatible with metallic fuels containing plutonium. Other properties of some of these materials, e.g., potential resistance to radiation damage and high-temperature creep strength, also provide the incentive for continued study of corrosion behavior. Of the refractory metals, vanadium has the best nuclear properties⁽²⁷⁾ and, therefore, has received most of our attention.

Corrosion specimens have been exposed in the oxygen-refreshed autoclave systems described last year (ANL-7155) and in a dynamic loop facility (Figure 63). In all tests the vanadium alloy specimens were added and removed and the sodium samples for oxygen analysis taken with the system at operating temperature, usually 650°C. Analytical samples of the sodium were removed in electropolished stainless steel or chemically polished nickel tubes. A plunger within the sampling tube, actuated from outside the test system, permits the inside of the tube to be flushed several times with bath sodium before retrieval of a sample. The sodium sample was extruded, amalgamated and washed with mercury under vacuum ($\sim 4 \times 10^{-6}$). Precautions were taken to minimize contamination during the analysis. Because of the high sampling temperature, sodium monoxide was assumed to be the source of the alkalinity determined by titration.

Alloys were made by levitation melting (small ingots) or by multiple arc melting. The levitation melts were tested in the "as chill cast" condition with machined, lightly etched surfaces. The larger arc melted castings were fabricated into sheet and tested with various heat treatments. Most of the samples were wet ground (240 grit) and lightly etched before corrosion testing.

The oxygen level of the sodium chosen for corrosion exposures in the more recent tests has been keyed to that expected or obtained in the EBR-II reactor. EBR-II sodium samples analyzed by our technique first showed about 13 wt. ppm and more recently about 6 wt. ppm oxygen. Some of our earlier experiments had been performed at higher levels with the purpose of accelerating the rate of screening of alloys by corrosion resistance. However, as will be shown, it is now believed that this concept (of "accelerated" testing) is not valid.

⁽²⁷⁾ Okrent, D., Nuc. Met. (AIMF) **9**, 1-56, 1963 (IMD Special Report Series No. 12); also Power Reactor Tech., **7**(2), 128-133, 1964.

106-8974

FIG 60. Variation of the Parabolic Rate Constant of V-20w/oTi in Sodium Containing 1-6 ppm Oxygen with Temperature.

45151

350X

FIG 61. V-20w/oTi Exposed for 40 Hours to Sodium at 650°C Containing 6 wt ppm Oxygen. The layers at the top are aluminum backing foil used to protect the edge of the specimen during polishing. In the lower (alloy) layer the diamond-shaped impressions left by the indents of a hardness tester decrease in size as the edge is neared, where the hardness is greater.

106-8977

FIG. 62. Hardness Profiles for V-20Ti Exposed to Sodium under Various Conditions of Time and Temperature.

All of the vanadium alloys have shown great sensitivity to oxygen level in the sodium with a sharp break in corrosion behavior at about 10 wt. ppm. The characteristic mode of attack noted above this level will be discussed first.

(1) Corrosion in Sodium Containing >10 ppm Oxygen

Vanadium reacts directly with the dissolved oxygen in sodium to form a $\text{VO}_{0.9}$ phase at oxygen levels greater than about 10 ppm. The vanadium oxide forms a relatively nonprotective and nonadherent coating. Alloying additions of Ti, Cr, and Al have been shown to reduce the rate of attack under these conditions, probably by forming more protective mixed-oxide

coatings. For example, the corrosion of V-20w/oTi proceeds at a linear rate (Figure 64) in static refreshed systems. The alloy also picks up oxygen from the sodium, forming a hardened zone of dissolved oxygen in the metal just under the surface. The depth of this diffusion zone tended to remain roughly constant with time when the corrosion rate was linear (Table 32).

A few short (7-day) dynamic experiments at 650°C, 6.1 meter/sec velocity showed that the corrosion process was also velocity sensitive above ~10 ppm oxygen. For example, erosive effects and significant thinning (100 μ per side) of the V-20w/oTi specimens occurred in a one week test at 20 to 28 ppm. Exposure in a refreshed static system at the same oxygen level would be expected to lead to only about 30 to 40 μ thinning.

FIG. 63. Liquid Sodium Test Loop.

106-8979

The difference between static and dynamic corrosion results was sharply reduced as the oxygen content of the system was lowered. At 15 ppm oxygen, the dynamic test specimens lost only 10 to 18 μ per side in a one week test, while static exposure samples lost $\sim 10 \mu$ at the same oxygen level during a one week exposure.

Improvements in corrosion resistance were obtained by alloying with both chromium and aluminum. As shown in Table 33 sizable additions of both elements are necessary to achieve low weight changes. The results of longer corrosion exposures for a few of the alloys are shown in Figure 65. The relatively sharp subsurface diffusion zone that is characteristic of V-20w/oTi is not noted with these alloys.

Unfortunately, the ternary V-Cr-Al alloys are very difficult to fabricate. An effort was made to modify V-20Cr-10Al with Zr (1 w/o) or Y (0.5 w/o), but no marked improvement in fabrication resulted. The corrosion resistance in 25 to 30 ppm oxygenated sodium at 650°C was not altered by the modifying additions.

One further attempt to improve the fabricability involved adding sizable amounts of titanium to the ternary. As shown in Table 34 the titanium additions in-

106-8976

FIG. 64. Behavior of V-20w/oTi (Annealed Sheet) in Oxygenated Sodium.

creased somewhat the weight loss of the V-20Cr-10Al composition. In addition, the presence of titanium reintroduced the subsurface hardened band. No serious attempt was made to fabricate the alloys in view of the latter development.

TABLE 32. DEPTH OF HARDENED LAYER ON V-20w/oTi CORRODED IN SODIUM AT 650°C

Time, days	Sodium Oxygen Level, ppm	Layer, μ
7.0	15	38-42
14.0	15	49-55
21.1	14	45-58
28.1	16	44-57
35.1	16	45-60
42.1	12	50-65

As has been shown (ANL-7155), V-Cr binaries do not show improved corrosion resistance as compared with V-Ti binaries at relatively high oxygen concentrations. However, as will be seen in the next section, the relative behavior is markedly different at lower oxygen concentrations. Therefore, an experiment was performed to observe the effect on relative corrosion resistance of changes in oxygen concentration across the concentration level of sharp change in corrosion behavior, i.e., approximately 10 ppm. Sheet samples were first exposed to oxygen-refreshed sodium at 650°C with a cold-trap temperature of 120°C for one week. The same samples were ground free of corrosion product and re-exposed to oxygen refreshed sodium at 650°C with a cold-trap temperature of 170°C for an additional week. The results are summarized in Table 35. It is apparent that the relative corrosion positions shift as the oxygen content of the sodium is changed.

TABLE 33. CORROSION BEHAVIOR OF V-Cr-Al TERNARY ALLOYS IN STATIC REFRESHED SODIUM AT 650°C

Alloy	Oxygen Conc. in Sodium, ppm	Weight Change, mg/cm ²
V-10Cr-10Al	25-35	-10.7
V-20Cr-5Al	25-35	-20.7
V-20Cr-7.5Al	25-35	-13.0
V-20Cr-10Al	25-35	-1.8, -2.2
V-25Cr-5Al	25-35	-15.8
V-30Cr-5Al	25-35	-6.0
V-30Cr-7.5Al	25-35	-5.1
V-30Cr-10Al	25-35	-1.8
V-20Ti (Reference Annealed Sheet) ^(a)	25-35	-19.0, -20.9
V-30Cr-5Al	15-18	-.40
V-30Cr-7.5Al	15-18	-1.8
V-40Cr-10Al	15-18	-0.2
V-20Ti (Reference Annealed Sheet) ^(a)	15-18	-8.4

^(a) Rolled and annealed at 900°C. 7.0 days exposure—alloys tested as levitation melted, chill cast, and machined.

The value of "accelerated" tests is thus open to question.

(2) Corrosion in Sodium of Low Oxygen Content (<10 ppm)

An entirely different corrosion behavior is noted when the oxygen content of the sodium is reduced below 10 ppm. There is no direct formation of massive vanadium oxide, although the specimens do develop

FIG. 65. Comparison of the Corrosion of V-Cr-Al Alloys with that of V-20Ti.

stains or thin films after extended exposure. The corrosion damage is limited to the slow solution and diffusion of oxygen into the refractory alloy. In this region the effect of velocity is minimal and protective kinetics are obtained even with rapid flow (Figure 66). For most of the alloys no dimensional changes or evidence of corrosion-product loss were detected; thus the weight gains fairly represent the relative resistances of the alloys to the pickup of impurities, mostly oxygen, from the sodium. This was true for the V-5w/oCr alloy for the first 57 days of exposure but, at the next inspection (85 days) tiny flakes of material could be observed coming loose when the surface of this alloy was lightly scratched.

In exposures of up to 57 days, the V-5w/oCr is about an order of magnitude more resistant than the other alloys. V-15w/oTi-7.5w/oCr gained 80% and unalloyed vanadium about 33% of the V-20w/oTi reference weight gains at equivalent exposure. Taken together, these data suggest that in sodium with a relatively low oxygen level, chromium is a beneficial addition to vanadium and titanium is not. However, as shown earlier, titanium was shown to be one of the better alloying additions, if the oxygen level of the sodium exceeds about 15 ppm.

A probable explanation for the apparently contradictory behavior of titanium as an alloying additive for vanadium lies in the relative affinity of the metals for oxygen. At 650°C titanium is capable of forming titanium oxide in sodium containing <1 ppm oxygen while vanadium does not form an oxide phase until the oxygen level in the sodium exceeds about 10 ppm. Chromium has shown no oxide in sodium containing ~20 ppm oxygen.

Thus, in sodium whose oxygen concentration is less than 10 ppm, the greater oxygen affinity of titanium (in the V-Ti alloys) provides an added driving force for the pickup of oxygen. As mentioned before, above about the 10 wt. ppm oxygen level in the sodium, the vanadium itself reacts rather rapidly to form an oxide layer. The presence of titanium in the alloy and sub-

TABLE 35. CORROSION^(a) OF V ALLOYS IN 650°C SODIUM

Alloy	Weight Change, mg/cm ²	
	C.T. 120°C (8.2, 7.5 ppm O)	C.T. 170°C (15 ppm O)
V-15Ti-10Cr Annealed	+0.19	-9.6
V-15Ti-10Cr 40% cold work	+0.26	-10.0
V-15Ti-12.5Cr Annealed	+0.16	-8.7
V-15Ti-12.5Cr 40% cold work	+0.16	-8.6
V-40Ti-10Cr 50% cold work	+0.25	-5.2
V-20Ti Annealed	+0.48	-7.3

^(a) Each exposure 7.0 days.

sequently titanium oxide in the corrosion coating apparently improves the protective character of the rather loosely adherent oxide layer and provides a better diffusion barrier to the corrosion reaction. In both cases, the diffusion of oxygen into the bulk of the specimen is retarded by the titanium addition, resulting in a highly oxygen-enriched zone near the surface. Chromium also retards oxygen-diffusion in V-Cr alloys but, because of its lower chemical affinity for oxygen, does not provide an increased driving force for oxygen pickup from sodium.

A short series of experiments was performed in order to make certain the excellent corrosion behavior of V-20w/oTi in the cold-trapped loop sodium at 650°C was not due to total depletion of oxygen available to the system. About 1 gm of Na₂O₂ was added to the loop sodium at 650°C and the system was operated without refractory alloys for three days with the cold trap at 120°C (as indicated by a thermocouple on the outside wall).

The initial one week exposure of fresh V-20w/oTi coupons at 650°C, 6.1 meter/sec (9 ppm terminal oxygen) gave higher than expected corrosion results. Even so, these results were significantly lower than previously reported for a 15 ppm oxygen dynamic test. It was felt that perhaps the time allotted for transfer of the oxygen into the cold trap (three days) was too short since one gm of Na₂O₂ would result in a 300-400 ppm concentration initially.

A second one week exposure with fresh samples produced the expected low corrosion weight gains of the same order as those plotted in Figure 66. Terminal oxy-

TABLE 34. CORROSION OF V-20Cr-10Al-Ti ALLOYS IN STATIC REFRESHED SODIUM AT 650°C CONTAINING ~16 PPM OXYGEN

Alloy	Weight Loss, mg/cm ²
V-20Cr-10Al ¹	1.54
V-20Cr-10Al-5Ti	2.15
V-20Cr-10Al-10Ti	1.64
V-20Cr-10Al-15Ti	2.77
V-20Cr-10Al-20Ti	3.13
V-20Ti ^(a)	7.14

^(a) Rolled and annealed at 900°C. 7.0 days—alloys tested as levitation melted, chill cast, and machined.

106-9216

FIG. 66. Corrosion of Vanadium Alloys in Flowing Sodium (6.1 meter/sec) at 650°C Oxygen Level ~ 10 ppm.

gen concentration was 10 ppm (by mercury amalgamation analysis). This provides evidence that the good corrosion behavior with vanadium alloys can be achieved in a cold trapped sodium system with oxygen concentrations of the order of those measured in the EBR-II reactor.

The exact value of the oxygen concentration in such cold trapped systems is still open to question. The data we have accumulated over the past three years indicate the precision of the mercury amalgamation method is adequate for our purposes; however, the accuracy is unknown. Recent work by other members of our group indicates the mercury amalgamation technique may be sensitive to other sodium compounds in addition to the oxide. Hence, the reported oxygen concentrations of cold-trapped sodium may be somewhat high. Distillation analyzers are being made integral components of all our test equipment but conclusions based on the use of cold-trapped sodium are independent of the method of analysis.

(3) Other Metals

A 70-day comparison test of six unalloyed metals in static oxygen refreshed sodium at 650°C (cold trapped to an oxygen content of 9 to 11 ppm) has been completed. The weight-change data are summarized in Table 36. It is clear that molybdenum and chromium are quite resistant under these conditions. It may be (based upon results with stainless steel) that chromium tested under conditions more conducive to mass transfer would suffer greater losses.

e. EXPOSURE OF V-20w/oTi CREEP SPECIMENS TO SODIUM (C. F. CHENG AND J. C. TEZAK)

We have exposed specimens of V-20w/oTi to sodium and have interpreted the corrosion and oxygen dissolution behavior. The creep data are reported elsewhere.

Creep specimens (900°C annealed sheet) were exposed in sodium at 650°C at two oxygen concentration levels.

- (1) Approximately 20 wt. ppm for 7 days—15 cm/sec sodium velocity.
- (2) Less than 10 wt. ppm for periods of 7 and of 21 days—static sodium.

The samples were initially stressed as the result of the differential thermal expansion between the stainless steel sample holders and the V-20w/oTi samples. After exposure to sodium the samples were subjected to uniaxial creep tests in vacuum (4×10^{-7} to 5×10^{-6} torr) at 650°C and a stress of 15 kg/mm² (based on original data). These results were compared with those obtained for unstressed samples maintained at 650°C in vacuum for seven days.

The weight change data were consistent with those previously observed for V-20w/oTi. At 20 ppm oxygen there was a weight loss of 1.81 mg/cm². At the low oxygen (<10 ppm) level there were weight gains of 1 to 2 mg/cm². All samples showed an increase in surface hardness. The specimen exposed at the 20 ppm concentration was reduced in cross-sectional area by about 20%.

The hardness profiles of the above and of related samples are given in Figure 67. The hardened layer is thicker after a given period of exposure for samples exposed in "high" oxygen sodium as compared with those exposed in "low" oxygen sodium. Cross-plotting of the data of Figure 67 indicates that the rate of growth with time of the hardened layer yields a straight line on a logarithmic plot. The slope of the "20 ppm" line is higher than that of the "<10 ppm" line.

The creep strength of the sample exposed in 20 ppm oxygen sodium was considerably reduced, even allowing for the decrease in load bearing area. However, the creep strength of the samples exposed in sodium containing <10 ppm oxygen was not reduced. It is of ob-

106-9217

FIG. 67. Hardness Profiles of V-20w/oTi in 650°C Sodium Exposure.

vious importance to learn if the degradation of creep behavior is directly related to a specific thickness of the hardened layer. Samples are now being exposed in "low oxygen" (<10 ppm) sodium for times calculated to result in hardened layers approximately 30 microns thick (the approximate thickness of the hardened layer produced after seven days in 20 ppm oxygen sodium).

f. UNIAXIAL AND BIAXIAL CREEP OF V-20 w/oTi EXPOSED TO SODIUM (F. L. YAGGEE AND E. R. GILBERT)

Publications

Yaggee, F. L. and Gilbert, E. R., *Selection of Fuel Jacket Materials for Sodium-Cooled Fast Reactors*. (Presented at the Third ASME Materials Symposium on May 9, 1966, Idaho Falls, Idaho.)

Yaggee, F. L. and Gilbert, E. R., *Effects of Sodium Exposure on the Mechanical Properties of Potential Fuel Jacket Materials at 550–700°C*. (Presented at the IAEA Sponsored Symposium on So-

TABLE 36. BEHAVIOR OF UNALLOYED METALS IN SODIUM AT 650°C

Metal	Weight Change, mg/cm ² at Indicated Time, Days					
	7.8	14.8	28.0	42.0	56.0	70.0
Chromium	−0.04	−0.04	−0.04	−0.04	−0.04	−0.08
Molybdenum	0	0	0	−0.03	−0.03	−0.03
Niobium	−0.11	−0.18	−0.63	−1.5	−2.1	−2.5
Tantalum	−1.5	−3.0	−7.6	−10.1	−11.8	−14.4
Titanium	+0.39	+0.33	−0.39	−0.99	−1.7	−2.3
Vanadium	+0.18	+0.15	−0.07	+0.11	+0.19	+0.22
Sodium	Oxygen Content (Hg Amalgamation), wt. ppm at Indicated Time, Days					
	—	10.7 9.5	10.3	—	11.3	9.3

dium Corrosion, November 28–December 2, 1966, Vienna, Austria, Paper SM-85/21.)

(1) Introduction

Program work on the development of fuel-jacket materials for use in liquid-metal cooled fast breeder reactors (LMFBR) was continued. Principal effort was directed toward the vanadium-base alloys in the following areas:

- (1) Effect of heat treatment on the uniaxial creep of V-Ti and V-Ti-Cr alloys.
- (2) Uniaxial tensile properties of V-15w/oTi-7.5w/oCr at constant strain rate.
- (3) Stress and temperature dependence of the minimum creep rate of V-15w/oTi-7.5w/oCr.
- (4) Effect of sodium exposure on the uniaxial and biaxial creep of V-20w/oTi.

Some effort was also expended to determine the effect of sodium exposure on the biaxial creep of Type 304 stainless steel and Nb-1w/oZr. The creep properties of most of these materials before sodium exposure have already been reported.^(28,29)

The thermal-expansion characteristics of vanadium-base alloys were determined for a variety of alloy compositions as part of the program work. Likewise, the creep behavior of Type 318 stainless steel* was determined before and after extended exposure to high-pressure steam at 650°C. Interest in Type 318 stainless steel is based on its strength advantage over Type 304 stainless steel at 650°C. Its use would be restricted to those applications where additional creep strength is desirable but compatibility between the fuel and the jacket material is not a limiting factor.

(2) Uniaxial Creep

Sheet specimens (0.45 mm thick) of 900°C annealed V-20w/oTi were exposed to flowing sodium at 650°C for periods of 7 and 21 days and their creep behavior thereupon compared to control specimens given a comparable anneal in vacuum. Creep tests were conducted in vacuum at 650°C and stresses of 15 and 30 kg-mm⁻². Some specimens were subjected to a relaxing stress during the sodium exposure, while others were exposed simultaneously without stress. The stress-relaxation method of specimen loading simulates the relaxing thermal stress experienced by a reactor fuel jacket while in service. This method takes advantage of the difference in thermal expansion between the stainless steel stressing fixture and the specimen.

⁽²⁸⁾ Annual Report for 1964, Metallurgy Division, ANL-7000, pp. 78–80.

⁽²⁹⁾ Annual Report for 1965, Metallurgy Division, ANL-7155, pp. 33–36.

* The composition of the Type 318 stainless steel, in w/o, is: 0.08 max. C, 2.0 max. Mn, 0.75 Si, 11–14 Ni, 16–17.75 Cr, 2–3 Mo, 0.03 max. P, 0.007 max. S, and 9XC Nb.

The combined effect of stress and exposure to high-oxygen sodium (20 wt. ppm O₂) results in a considerable increase in specimen creep rate and a decrease in rupture life. Specimens similarly exposed in the unstressed state exhibit a creep rate and a rupture life between that of the control specimen and that of specimens exposed to sodium under stress. These deleterious effects of sodium exposure are more pronounced in creep tests conducted at 30 kg-mm⁻² stress as compared to those conducted at 15 kg-mm⁻² stress. Specimens exposed under stress to low-oxygen sodium (10 wt. ppm O₂) are not as seriously affected, even when such exposure is extended to longer times. The surface oxide formed on specimens exposed to high-oxygen sodium is thick, severely cracked and only moderately adherent, thereby seriously reducing their effective load-bearing cross section. In contrast the surface oxide formed on specimens exposed to low-oxygen sodium is considerably thinner and significantly more adherent.

The effect of sodium purity (20 wt. ppm O₂ versus 10 wt. ppm O₂) on the uniaxial creep of V-20w/oTi is illustrated in Figure 68 for specimens tested at 650°C and 30 kg-mm⁻² stress. Exposure to high-oxygen sodium has the effect of decreasing creep strength, rupture life and ductility.

(3) Biaxial Creep

The biaxial creep behavior of thin wall (0.38 mm wall) V-20w/oTi tubing stressed by internal gas pressure has been reported.⁽²⁹⁾ Similar tubing was exposed at 650°C to flowing sodium containing 20 ppm oxygen (high oxygen sodium) for seven days, both under stress and without stress. The stress-relaxation method of specimen loading (axial direction) is similar to that used for sheet specimens.

The effect of stress and exposure to high-oxygen sodium on the biaxial creep behavior of V-20w/oTi tubing tested at 650°C and 30 kg-mm⁻² stress is illustrated in Figure 69. The relative decreases in creep strength and rupture life are comparable to those observed for this alloy in uniaxial tension. However, the slight increase in rupture ductility indicated in Figure 69 is contrary to the decrease in rupture ductility observed for this alloy in uniaxial tension after a similar exposure history. The oxide surface layer that is formed during sodium exposure (≈ 0.001 inch thick) is cracked, but these cracks are not easily propagated through the V-20w/oTi matrix.

g. EFFECT ON BIAxIAL CREEP OF EXPOSURE OF TYPE 304 STAINLESS STEEL AND Nb-1w/oZr TUBING TO SODIUM (F. L. YAGGEE, E. R. GILBERT AND J. W. STYLES)

The biaxial creep behavior of thin-wall (0.38 mm wall) Type 304 stainless steel and Nb-1w/oZr tubing stressed by internal gas pressure has been re-

ported.^(28,29) Similar tubing of stainless steel was exposed to low-oxygen sodium (10 ppm O_2) in the absence of stress, while Nb-1w/oZr tubing was exposed to high-oxygen sodium (20 ppm O_2) both under stress and without stress. The sodium exposures were made at 650°C for a period of seven days.

(1) Biaxial Creep of Type 304 Stainless Steel

The effect of exposure to low oxygen-sodium on the biaxial creep of stainless steel at 550°C and 25 to 28 kg-mm⁻² stress is illustrated in Figure 70. Tube specimens pre-exposed to sodium are more ductile and have a longer rupture life than the control specimens. A slight decrease in creep strength is also noted as a result of sodium exposure.

(2) Biaxial Creep of Nb-1w/oZr

Nb-1w/oZr is completely embrittled by exposure to high-oxygen sodium while under load. The biaxial creep behavior of Nb-1w/oZr at 700°C and 30 to 31 kg-mm⁻² stress is shown in Figure 71. After sodium exposure the strain at rupture is approximately 0.1 percent and the rupture life is less than two hours. In contrast the control specimens show rupture strains that are 30 to 70 times greater, and rupture lives that are 35 to 110 times longer. The surface oxide formed on Nb-1w/oZr during exposure to high oxygen sodium is heavily textured and severely cracked. These cracks are easily propagated into the alloy matrix indicating the extreme notch sensitivity of Nb-1w/oZr.

h. LINEAR THERMAL EXPANSION OF VANADIUM, TITANIUM, CHROMIUM, AND SOME VANADIUM-BASE BINARY AND TERNARY ALLOYS (F. L. YAGGEE AND J. W. STYLES)

Information on the thermal-expansion characteristics of fuel-jacket materials is of interest both in fuel

106-9019

FIG. 68. Effect of Sodium Purity on Creep of V-20w/oTi Sheet Specimens at 650°C and 30 kg/mm² Stress (20 versus 10 ppm O_2).

106-9016

FIG. 69. Creep of V-20w/oTi Tube Specimens at 650°C and 30 kg/mm² Stress after Exposure in Sodium (20 ppm O_2).

(a)

(b)

106-9020

FIG. 70. Creep of Stainless Steel (Type 304) Tube Specimens at 550°C after Exposure in Sodium (10 ppm O_2). a. 25.5 kg/mm² stress and b. 28.1 kg/mm² stress.

106-9015

FIG. 71. Creep of Nb-1w/oZr Tube Specimens at 700°C and 30 and 31.5 kg/mm² Stress.

element design and in the surveillance of fuel element performance. The linear thermal expansion behavior of V, Ti, Cr, V-30w/oTi, V-40w/oTi, V-50w/oTi, V-15w/oTi-7.5w/oCr, and V-5w/oTi-15w/oCr was determined between 25°C and 1000°C. Thermal expansion data on V-20w/oTi for a comparable temperature range have already been reported.⁽²⁸⁾ The total interstitial impurity content for these materials, with the exception of chromium, is between 1000 and 1900 ppm by weight. The interstitial impurity analysis for chromium is 285 ppm.

The mean expansion coefficients for these materials in the temperature ranges 0°C to 500°C and 0°C to 1000°C are listed in Table 37.

i. EFFECT OF HEAT TREATMENT ON THE UNI-AXIAL CREEP STRENGTH OF VANADIUM-BASE ALLOYS (F. L. YAGGEE, E. R. GILBERT, AND A. R. BROWN)

(1) V-20w/oTi Alloy

The creep behavior of 900°C annealed V-20w/oTi sheet specimens (6.4 mm by 0.76 mm by 4.2 cm gage length) tested at 650°C and 15 kg-mm⁻² stress has been reported.⁽²⁸⁾ This alloy responds to heat treatment⁽³⁰⁾ as evidenced by a hardness minimum after a one-hour anneal at 900°C, and a subsequent increase in hardness

following anneals at temperatures above 900°C (all anneals are carried out in vacuum, 1×10^{-6} torr or better, for one hour). The change in size, distribution and morphology of the disperse impurity phase with time and temperature suggests that this alloy is capable of being dispersion strengthened.

Vanadium-20w/o titanium rod tensile specimens (6.4 mm diameter) were annealed at 700, 900, 1000, 1200, 1350, and 1500°C then creep tested at 650°C and 30 kg-mm⁻² stress (all creep tests conducted in a vacuum of 1×10^{-6} torr or better). The minimum creep rate decreases with increasing temperature of the anneal and with grain size as shown in Figure 72. It is not yet clear whether the grain size or the annealing temperature is the correlating parameter. The increase in creep strength (decrease in minimum creep rate) after a 1500°C anneal is attributed to solution strengthening by partial dissolution of the disperse impurity phase. The resulting grain size (0.8 mm) is larger than the 0.37 mm wall thickness of a typical tubular fuel jacket, and is therefore undesirable. In contrast the 1000°C anneal results in the longest rupture life, the largest ductility and the highest creep strength that is consistent with a practical grain size (≈ 0.03 mm).

Creep data generated at ANL for 1200°C annealed V-20w/oTi is compared in Figure 73 to other creep

TABLE 37. MEAN LINEAR THERMAL EXPANSION COEFFICIENTS FOR VANADIUM, CHROMIUM AND SOME VANADIUM-BASE ALLOYS

Material	Density (g-cm ⁻³)	Temperature Range (°C)	Mean Linear Expansion Coefficient (10 ⁻⁶ °C ⁻¹)
Vanadium	6.08 ± 0.01	0-500 0-1000	9.81 10.59
Titanium	4.51 ± 0.02	0-500 0-1000	9.57 10.61
Chromium	7.16 ± 0.01	0-500 0-1000	7.80 9.85
V-30w/oTi	5.53 ± 0.01	0-500 0-1000	10.04 11.18
V-40w/oTi	5.36 ± 0.03	0-500 0-1000	9.77 10.96
V-50w/oTi	5.20	0-500 0-1000	10.51 11.27
V-15w/oTi-7.5w/oCr	5.88 ± 0.02	0-500 0-1000	9.78 10.76
V-5w/oTi-15w/oCr	6.16	0-500 0-1000	10.38 11.50

⁽³⁰⁾ Kramer, W. C., Burt, W. R., Jr., Karasek, F. J., Flinn, J. E., and Mayfield, R. M., *Vanadium Alloy Screening Studies and the Fabrication of V-15w/oTi-7.5w/oCr Tubing for Nuclear Fuel Cladding*, ANL-7206.

47958

Fig. 72. Effect of Annealing Temperature on Minimum Creep Rate of V-20w/oTi Tested at 650°C and 30 kg/mm² Stress.

data generated at WANL.⁽³¹⁾ The temperature-compensating Zener-Hollomon parameter shows good agreement between creep data at 650°C and that at 700°C and 800°C.

(2) V-15w/oTi-7.5w/oCr and V-5w/oTi-15w/oCr Alloys

The V-15w/oTi-7.5w/oCr and V-5w/oTi-15w/oCr alloys respond to heat treatment in a manner similar to that observed for V-20w/oTi. Sheet specimens (0.76 mm thick) of the first alloy were annealed at 900, 1100, 1250, and 1500°C, while similar specimens of V-15w/oTi-15w/oCr were annealed at 1250°C only. Both alloys were creep tested at 650°C and 30 kg-mm⁻² stress. The 1250°C anneal is considered optimum for both alloys because it results in the desirable combination of a favorable grain size (≈ 0.05 mm), a low minimum creep rate and a fair rupture ductility. At 700°C and 30 kg-mm⁻² stress the experimentally determined minimum creep rates of V-5w/oTi-15w/oCr, V-15w/oTi-7.5w/oCr and V-10.4w/oNb-1.27w/oZr-0.049w/oC⁽³¹⁾ are in the approximate ratio of 1 to 5 to 6.

⁽³¹⁾High Strength Vanadium Alloy Project, Fourth Quarterly Progress Report, WCAP-3487-13.

j. UNIAXIAL TENSILE PROPERTIES OF V-15w/oTi-7.5w/oCr AT CONSTANT STRAIN RATE (F. L. YAGGEE, E. R. GILBERT, J. E. FLINN, AND A. R. BROWN)

The tensile properties of 1250°C annealed V-15w/oTi-7.5w/oCr were determined for the temperature range 25°C to 800°C for a constant strain rate of 2×10^{-4} sec⁻¹. Young's modulus (E), ultimate tensile strength ($S_{ult.}$), 0.2 percent offset yield stress (S_{yield}), reduction in area, total elongation (e), uniform elongation (ϵ), strain hardening exponent (n) and the strength coefficient (K) were determined at the various test temperatures from the load-elongation data. The ultimate tensile strength and 0.2 percent offset yield stress decrease with increasing temperature except in the range 200°C to 400°C where both show a slight increase due to strain aging. Young's modulus decreases more gradually with temperature and is unaffected by the strain aging.

True stress-true strain curves for the various test temperatures are shown in Figure 74. The waviness exhibited by the curve at 400°C in the region of approximate uniform plastic deformation (i.e., where $0.002 < \epsilon \leq n$) is attributed to strain aging. A parabolic flow stress is assumed to operate in this plastic strain region (i.e., $\sigma = K\epsilon^n$). At 200°C and 400°C the

47955

Fig. 73. Zener-Hollomon Parameter Versus Stress for V-20w/oTi Annealed at 1200°C.

47952

FIG. 74. True Stress Versus True Strain for V-15w/oTi-7.5w/oCr Annealed at 850°C for 1 hr (Strain Rate 2×10^{-4} sec $^{-1}$.)

TABLE 38. MECHANICAL PROPERTY PARAMETERS FOR THE V-15w/oTi-7.5w/oCr ALLOY AT VARIOUS TEMPERATURES

Test Temp. (°C)	Reduction in Area (%)	Elongation (%)	Uniform Elongation (%)	Strain Hardening Exponent, n	Strength Coefficient, K (kg mm $^{-2}$)
Room	56	29	17.7	0.18	123
200	60	15.5	13	0.21	123
400	35	28	12.6	0.19	116
600	52	28	15.5	0.165	102
800	99	50	7	0.07	49

load-elongation curves exhibit a type of "serrated" profile that is associated with strain aging behavior. These serrations are not easily resolved on log-log coordinates. The strain aging tendency in V-15w/oTi-7.5w/oCr is believed to be greater at 400°C than at 200°C by reason of a larger serration-amplitude at 400°C. This difference in strain aging tendency explains the slightly higher plastic flow stress at 400°C shown in Figure 74.

Values for the total elongation, uniform elongation,

reduction in area, strain hardening exponent and strength coefficient are given in Table 38. The greatest change in these parameters occurs between 600°C and 800°C as was observed for the ultimate tensile strength and the 0.2 percent offset yield stress. Agreement between the uniform elongation and the strain hardening exponent is very good for all temperatures except 200°C and 400°C. Such agreement supports the validity of the assumed parabolic flow stress in the region of uniform plastic strain. Since the strain hardening exponent accounts only for strengthening occurring through plastic deformation, disagreement between the values for uniform elongation and the strain hardening exponent can be expected when strain aging contributes appreciably to the increase in material hardness. Such disagreement is indicated in Table 38 at 200°C and 400°C.

k. STRESS AND TEMPERATURE DEPENDENCE OF THE ACTIVATION ENERGY FOR THE CREEP OF V-15w/oTi-7.5w/oCr (F. L. YAGGEE, E. R. GILBERT, AND A. R. BROWN)

(1) Stress Dependence

The minimum creep rate in uniaxial tension for many metals and alloys can be defined by the following expressions:

$$\text{at low stresses} \quad \dot{\epsilon}_m = A\sigma^n$$

$$\text{at high stresses} \quad \dot{\epsilon}_m = A' \exp [\beta\sigma]$$

where:

$\dot{\epsilon}_m$ is the minimum creep rate

A , n , A' and β are constants at constant temperature

σ is the applied stress

The expression at low stress shows a linear relation between $\dot{\epsilon}_m$ and σ on log-log coordinates, while the expression at high stress shows a similar linear relation on semi-logarithmic coordinates. Garofalo⁽³²⁾ has suggested that the creep behavior of many metals and alloys (i.e. copper, aluminum, Al-3.1w/oMg and austenitic stainless steel) can be defined over a wider range of temperatures and stresses by the hyperbolic sine function $\dot{\epsilon}_m = [\sinh \alpha\sigma]^n$.

The minimum creep rates for 900°C annealed V-15w/oTi-7.5w/oCr tested at 650°C have been plotted as a function of stress on log-log, semi-log and log-log sinh coordinates over the stress range 15 to 60 kg-mm $^{-2}$. Each plot can be separated into two straight line segments indicating that none of these stress functions can fit all of the experimental points to a single linear relation between minimum creep rate ($\dot{\epsilon}_m$) and the applied stress (σ). A change in slope of such a plot can

⁽³²⁾ Garofalo, F., 1963 Trans. AIME, **227**, 351.

47956

FIG. 75. Temperature Dependence of the Minimum Strain Rate of V-15w/oTi-7.5w/oCr Annealed 1 hr at 900°C and Tested at 500°C to 850°C.

indicate a change in the rate-controlling deformation mechanism, but this possibility is discounted on the basis that only one activation energy has been determined over the indicated stress range as shown in Figure 75. The above stress functions apply to a single-phase material that strain hardens solely through the generation of dislocations resulting from plastic deformation. The fact that none of the stress functions accurately describes the creep behavior over the entire stress range suggests that the impurity phase contributes significantly to the creep strength of V-15w/oTi-7.5w/oCr, and that this contribution may be stress sensitive.

(2) Temperature Dependence

The minimum creep rate for V-15w/oTi-7.5w/oCr is plotted against reciprocal temperature in Figure 75. The activation energy for creep (Q) is 89,000 cal-mole⁻¹ and appears to be independent of stress and temperature within the indicated range of these test variables. A similar value for the activation energy for creep was determined for V-20w/oTi.

Lundy⁽³³⁾ reports an activation energy of 61,000 cal-mole⁻¹ for enhanced diffusion of vanadium below 1400°C, and 91,500 cal-mole⁻¹ for diffusion of ⁴⁸V in vanadium single crystals above 1600°C. An acti-

vation energy of 61,000 cal-mole⁻¹ for diffusion of titanium in vanadium below 1400°C was calculated from the data reported by Murdock.⁽³⁴⁾ Both values of 61,000 cal-mole⁻¹ are much too low to explain the creep of V-15w/oTi-7.5w/oCr by such mechanisms as dislocation climb or nonconservative motion of jogs unless it is assumed that the mechanism for enhanced diffusion does not affect the creep rate. If this assumption is correct then the experimental value of 89,000 cal-mole⁻¹ for creep is in good agreement with the value of 91,500 cal-mole⁻¹ reported by Lundy.

I. IRRADIATION OF FAST-REACTOR JACKET MATERIALS (R. CARLANDER AND W. F. MURPHY)

Since it has been only recently that fast-reactor experimental irradiation facilities have become available, investigations of the effects of fast neutron irradiation on the mechanical properties of fast-reactor jacket materials have been necessarily conducted in thermal reactors. The data obtained from these investigations have been generated from experiments primarily on austenitic stainless steels and high-strength nickel-base alloys, and these results have indicated that, at temperatures below approximately 500°C, the alloys undergo increases in strength and decreases in ductility that are related to irradiation-induced displacements. Above approximately 500°C, however, the low-temperature type of displacement damage is re-

⁽³³⁾ Lundy, T. S., *Diffusion in the Body-Centered Cubic Metals Zirconium, Vanadium, Niobium and Tantalum*, ORNL-3617 (June 1964).

⁽³⁴⁾ Murdock, J. F., *Annual Progress Report, Oak Ridge National Laboratory*, ORNL-3870 (November 1965).

TABLE 39. ARGONNE CLADDING MATERIALS IRRADIATIONS IN PROGRESS

Test Reactor	S/A No.	Capsule Number	Design Parameters				Operating Conditions	
			Cladding composition, w/o	Type of Specimen	No. of specimens	Specimen environment	Max. spec. temp., °C	Exposure to date, n/cm ²
EBR-II	XA08	AS-1	V-20Ti	Tube-burst	12	Argon-helium	540	3.4×10^{22}
EBR-II	XA08	AS-2	V-20Ti	Tube-burst	12	Argon-helium	540	3.4×10^{22}
EBR-II	XA08	AS-3	Hast.-X	Tube-burst	12	Argon-helium	540	3.6×10^{22}
EBR-II	XA08	AS-4	Hast.-X	Tube-burst	12	Argon-helium	540	3.6×10^{22}
EBR-II	XA08	AS-5	304 SS	Tube-burst	12	Argon-helium	540	3.6×10^{22}
EBR-II	XA08	AS-6	V-20Ti	Tensile	16	Argon-helium	580	3.7×10^{22}
EBR-II	XA08	AS-7	Hast.-X	Tensile	16	Argon-helium	580	3.4×10^{22}
EBR-II	XA08	AS-8	304 SS	Tensile	16	Argon-helium	580	3.4×10^{22}
EBR-II	XA08	AS-12	V-20Ti	Tensile	16	Argon-helium	580	3.3×10^{22}
EBR-II	X010	AS-16	V-20Ti	Tensile	13	Argon-helium	500	1.2×10^{22}
EBR-II	X010	AS-17	V-20Ti	Tensile	13	Argon-helium	500	1.3×10^{22}
EBR-II	X010	AS-18	V-20Ti	Tensile	13	Argon-helium	500	1.2×10^{22}
EBR-II	X010	AS-19	V-20Ti	Tensile	13	Argon-helium	500	1.2×10^{22}
EBR-II	X010	AS-20	V-20Ti	Tensile	13	Argon-helium	500	1.4×10^{22}
EBR-II	X010	AS-21	V-20Ti	Tensile	13	Argon-helium	500	1.6×10^{22}
EBR-II	X010	AS-22	Hast.-X	Tensile	13	Argon-helium	500	1.4×10^{22}
EBR-II	X010	AS-23	304 SS	Tensile	13	Argon-helium	500	1.6×10^{22}
EBR-II	X010	AS-24	304 SS	Tensile	13	Argon-helium	500	1.4×10^{22}
EBR-II	X010	AS-25	304 SS	Tensile	13	Argon-helium	500	1.3×10^{22}
EBR-II	X010	AS-26	304 SS	Tensile	13	Argon-helium	500	1.3×10^{22}
EBR-II	X018	AS-56	V-20Ti, V-15Ti-7.5Cr	Tensile, Tube-burst	75	NaK	650	4.0×10^{20}
EBR-II	X018	AS-57	304 SS, Hast.-X	Tensile, Tube-burst	75	NaK	650	4.0×10^{20}
EBR-II	X018	AS-58	V-20Ti, V-15Ti-7.5Cr	Tensile, Tube-burst	25	NaK	650	4.0×10^{20}

Note: Inner specimen capsules are constructed of Type 304 stainless steel, Hastelloy-X, Inconel 625, and V-15Ti-7.5Cr and will be used for tube-burst testing.

moved by annealing; and both thermally-induced effects and transmutations, attributed primarily to helium-generating n, α reactions, have a predominant effect on the mechanical properties—namely, small changes in strength but large decreases in ductility. These losses in ductility are of immediate concern in the elevated-temperature application of fast-reactor jacket materials since they are not recoverable and do not appear to saturate with increasing fast neutron exposure.

Argonne's investigation of the effects of fast neutron irradiation coupled with elevated temperature on the mechanical properties of fast-reactor jacket materials is concentrated on vanadium-base alloys since they exhibit promising elevated temperature properties in the temperature range desired for Liquid Metal Fast Breeder Reactors, and because of the favorable neutron characteristics of vanadium in fast breeder reactors. The irradiations are being conducted in EBR-II at temperatures between 400°C and 750°C in order

to span the temperature range that would be expected over the length of a fuel element and in which both the low-temperature type of damage and the high-temperature type of damage appear to occur. The investigations include irradiations to total integrated neutron exposures of 1×10^{21} to 1×10^{23} n/cm² in order to determine if the observed properties continuously change (as for austenitic stainless steels and nickel-base alloys) or tend to saturate at some exposure where some reasonable extrapolation can be made to higher exposures.

Recent work⁽³⁵⁾ has shown that although the ductility of V-20w/oTi alloy irradiated at 50°C to a fast neutron exposure of 1.4×10^{21} ($E_n > 0.1$ Mev) was decreased in room-temperature tests, the strength and

⁽³⁵⁾ Böhm, H., Dienst, W., Hauck, H., and Laue, H. J. *Irradiation Effects on the Mechanical Properties of Vanadium base Alloys*, Paper No. 75, presented at 69th Annual Meeting of ASTM, Atlantic City, New Jersey, June 27–July 1, 1966. (To be published as ASTM Special Technical Publication).

TABLE 40. ARGONNE CLADDING MATERIALS IRRADIATIONS COMPLETED

Test Reactor	S/A No.	Capsule Number	Design Parameters				Operating Conditions	
			Cladding composition, <i>w/o</i>	Type of specimen	No. of specimens	Specimen environment	Max. spec. temp., °C	Total exposure, <i>n/cm</i> ²
EBR-II	XA07	AS-9	V-20Ti	Tensile	16	Argon-helium	590	3.8×10^{22}
EBR-II	XA07	AS-10	Hast.-X	Tensile	16	Argon-helium	590	3.5×10^{22}
EBR-II	XA07	AS-11	304 SS	Tensile	16	Argon-helium	590	3.6×10^{22}
EBR-II	X009	AS-14	V-20Ti	Tensile	13	Argon-helium	670	2.6×10^{22}
EBR-II	X009	AS-15	V-20Ti	Tensile	13	Argon-helium	670	2.5×10^{22}
EBR-II	X009	AS-27	304 SS Hast.-X	Tensile	13	Argon-helium	670	2.7×10^{22}
EBR-II	X013	AS-34	Hast.-X	Tensile	9	Sodium	650	7.0×10^{21}
EBR-II	X013	AS-35	V-20Ti	Tensile	9	Sodium	650	6.5×10^{21}
EBR-II	X013	AS-36	V-20Ti	Tensile	9	Sodium	650	6.3×10^{21}
EBR-II	X013	AS-37	Hast.-X	Tensile	9	Sodium	650	7.0×10^{21}
EBR-II	X013	AS-38	V-20Ti	Tensile	9	Sodium	650	7.3×10^{21}
EBR-II	X013	AS-39	V-20Ti	Tensile	9	Sodium	650	7.0×10^{21}
EBR-II	X013	AS-40	V-20Ti	Tensile	9	Sodium	650	7.3×10^{21}
EBR-II	X013	AS-41	V-20Ti	Tensile	9	Sodium	650	6.5×10^{21}
EBR-II	X013	AS-42	V-15Ti-7.5Cr	Tensile	9	Sodium	650	6.5×10^{21}
EBR-II	X013	AS-43	V-15Ti-7.5Cr	Tensile	9	Sodium	650	6.8×10^{21}
EBR-II	X013	AS-44	V-15Ti-7.5Cr	Tensile	9	Sodium	650	6.8×10^{21}
EBR-II	X013	AS-45	V-15Ti-7.5Cr	Tensile	9	Sodium	650	6.5×10^{21}
EBR-II	X013	AS-46	Hast.-X	Tensile	9	Sodium	650	7.3×10^{21}
EBR-II	X013	AS-47	304 SS	Tensile	9	Sodium	650	7.5×10^{21}
EBR-II	X013	AS-48	304 SS	Tensile	9	Sodium	650	7.3×10^{21}
EBR-II	X013	AS-49	304 SS	Tensile	9	Sodium	650	7.3×10^{21}
EBR-II	X013	AS-54	V-15Ti-7.5Cr	Tensile	9	Sodium	650	6.8×10^{21}
EBR-II	X013	AS-55	V-15Ti-7.5Cr	Tensile	9	Sodium	650	7.0×10^{21}

Note: Inner specimen capsules are constructed of Type 304 stainless steel, Hastelloy-X, Inconel 625, and V-15Ti-7.5Cr and will be used for tube-burst testing.

ductility of the alloy when tested at 650°C were not significantly different from those of the unirradiated alloy. Vanadium-base alloys appear therefore to be promising candidate jacket alloys at the elevated temperatures applicable to fast-reactor systems.

The vanadium-base alloys chosen for study are those indicated to be the most promising relative to fabricability, corrosion resistance, and mechanical properties, and include, at present, V-20*w/o*Ti and V-15*w/o*Ti-7.5*w/o*Cr. The improved alloy V-15*w/o*Cr-5*w/o*Ti will be included when material becomes available. The tensile, creep, creep-rupture, and tube-rupture properties of these alloys will be evaluated as a function of irradiation temperature, postirradiation deformation temperature, fast neutron exposure, test environment, grain size, heat treatment, and strain rate in the short-time tensile tests. The results from the vanadium-base alloy experiments will be compared

to that observed for Hastelloy-X, Inconel 625, and AISI Type 304 stainless steel irradiated and tested under similar conditions.

The concentration of effort has been on initiating irradiations in EBR-II, particularly those requiring high exposures. The scope of the experiments are shown in Tables 39 and 40 and include irradiations at 500°C to 670°C at exposures from 6.3×10^{21} to 1×10^{23} *n/cm*². Irradiations at 400°C and 750°C are planned for the future and are dependent on the results obtained from tests on materials that have been irradiated as indicated in Table 40. Receipt of the first of the irradiated materials is expected early in 1967. One 5,000 kg Instron tensile-testing machine, seven instrumented Satec Model D creep machines of 20,000 lb. capacity, and one Argonne-built tube-burst apparatus have been procured and are being set up in hot-cell facilities for conducting the postirradiation studies.

6. Zero-Power Fuels and Fuel Elements

a. DEVELOPMENT OF ZERO-POWER PLUTONIUM REACTOR FUEL (A. B. SHUCK, H. F. JELINEK, A. G. HINS, AND N. J. CARSON, JR.)

The development of design, process and specification for ZPPR fuel elements was completed and the following specifications were issued:

ANL Specification No.	Title of Specification
PF-1600	Specification for Uranium-Plutonium-Molybdenum Alloy ZPPR Fuel Elements
PF-1607	Specification for Plutonium for ZPPR Fuel Elements
PF-1612	Specification for Uranium for ZPPR Fuel Element Fabrication
PF-1615	Specification for Plutonium Nitrate

The suitability of the above specifications to the practical fabrication of the ZPPR fuel elements was tested by developing methods for fabricating the elements and by proving these methods through pilot-lot manufacture of the fuel elements. A procedure was written that was followed closely for the manufacture of 73 fuel elements in lengths from 1 in. to 8 in. As this procedure is slightly different from the process previously described, it is summarized below:

(1) Synopsis of Process

The flow diagram for ZPPR fuel element manufacture is shown in Figure 76. The major steps of core plate manufacture are: (1) preparation of uranium-molybdenum binary alloy, (2) melting of the binary alloy with plutonium and casting into precision-sectioned bars, (3) parting core slugs from the bars, (4) milling the cores to precise lengths, (5) weight adjustment of the cores by chamfering the edges and milling to a variable width, and (6) cleaning the cores to prevent plutonium contamination of the jackets during final assembly operation. Accurate materials' accountability was practiced for all operations on the cores. Precise charge calculations and accurate weighing of all materials was required.

Alloy preparation and semiprecision casting were done in 10,000 Hz vacuum-induction furnaces. These furnaces consisted of 18 in. diameter lift bells containing the induction-coil assembly and a 6 in. deep furnace bottom. The crucibles were ogival-cavity MgO crucibles with bottom pour holes and stopper rods. A yttria coating was used to reduce attack by the molten metal. The crucibles were supported on MgO pedestals directly over the molds. The molds were yttria-coated graphite book molds having 4 or 6 cavities. One of these molds is shown in Figure 77. The cavities were

1.980 in. wide by 0.206 in. thick by 10 in. deep. The length of the mold assemblies used for pilot production were limited by the furnace configuration. A cavity 12.5 in. long would have allowed a greater yield of core plates per casting. The molds were supported on a zirconia slab, which rested upon the water-cooled furnace bottom. Porous alumina tiles were used around the mold for thermal insulation while the top of the mold extended into the induction coil.

The pilot-run melts were made on 6 kg charges. In full production the amount of alloy made per melt should be increased to a maximum of about 10 kg of ternary alloy containing about 3.3 kg of plutonium. The melting and casting parameters were as in Table 41.

The steps of jacket sleeve fabrication are: (1) roll forming and welding the stainless steel strip into welded tube, (2) die flattening the tube, (3) die forming the longitudinal edges of the tubes, (4) stretch forming the tube in a precision box die by means of an expanding mandrel, and (5) cutting the tubes to the length required for individual jacket sleeves. The end plugs were cut from draw-formed Type 304L stainless steel wire and were furnished to precision tolerance by grinding and milling. All jacket components were thoroughly cleaned.

Contamination-preventive methods were practiced in the assembling and welding of the fuel elements. After thorough brushing and wiping of the core plates to remove loose metal or oxide dust they were transferred to a contamination-free assembly glovebox. Clean jackets were moved into the area and the bottom plug was installed and welded in place. The jacket sleeves were installed in the welding chills and aluminum-foil funnels were inserted into the jacket opening. This prevented contact between the jacket lip and core plate during loading and minimized contamination of the weld area. The core plates were handled by special tongs and fixtures in such a way that the jackets and contamination-free areas were not contaminated by the plutonium.

The cores had to be loaded into the jacket sleeves quite slowly so that the displaced air would not blow particulate contaminants out of the jacket. The lip of the jacket and surrounding areas were cleaned with cotton swabs after loading, and the swabs were alpha counted.

Welding was done in a chamber that could be evacuated and back-filled with argon-helium gas mixture to less than $\frac{1}{2}$ atmosphere of pressure. Copper chills contacted all sides of the element during welding to prevent the expansion of the gas within the element and

FIG. 76. Flow Diagram—Manufacture of ZPPR Fuel Elements.

possible weld contamination or blowout. A spring plunger in the chill-fixture column loaded the assembly with about 40 pounds of force as the top end plug was welded in place. All the movements of the welding machine were mechanically controlled and programmed. The weld was made by fusing the edge of the jacket plug and the end sleeves by means of a DC-arc drawn

from a tungsten electrode. The chills and welding parameters were adjusted so that the radiused beads were made without buildup.

Inspection operations were carried out at each step of the process for quality-control purposes. Micrometers, surface gages, and comparators were used for pilot-lot inspection in order to obtain data, but go,

FIG. 77. Molds for ZPPR Castings.

TABLE 41. ALLOYING AND CASTING PARAMETERS

Charge composition	U-3.70w/oMo	U-28.25w/oPu-2.5w/oMo
Time, start to melt	40 min.	40 min.
Melt to superheat	30 min.	30 min.
Alloy liquidus, approximately	1160°C	1020°C
Alloy solidus, approximately	1125°C	920°C
Superheat temperature	1475°C	1350°C
Casting temperature ^(a)	1400°C	{ 1325°C 1285°C
Mold Temperatures before Casting		
Bottom	150°C	200°C
Top	450°C	600°C
Vacuum, torr	10 ⁻⁴	10 ⁻⁴

^(a) The pouring temperature was reduced during the pilot run operation to minimize the formation of shrinkage depressions on the faces of the castings.

no-go gages will be used in production. The core plates and jacketed elements were weighed on precision balances. The jackets were leak-detected by bubble testing and by mass spectrometer.

A number of provisions of the specifications were changed as a result of the pilot operation. The specification was rewritten to liberalize the composition and homogeneity requirements and some of the dimensional tolerances were increased in order to make the speci-

cations more realistic for commercial production. Although there was insufficient production to optimize the yield, Table 42 shows a material balance based upon selected melt from the later melts of the pilot production tests. The amount of the material-to-residue recovery should be reduced from the 7% shown by the table. The overall process loss of 0.4% is based upon the assumption that only 80% of what is thought to be in the residual scrap can be recovered. No unexpected difficulties were experienced with the process. Approximately 10% of the welds showed plutonium contamination although this was reduced to less than 2% on a similar batch of 200 fuel elements made with 22.3% ²⁴⁰Pu plutonium.

b. FABRICATION OF ZERO-POWER REACTOR FUEL FROM PLUTONIUM DERIVED FROM HIGHLY IRRADIATED FUEL (N. J. CARSON, JR., A. G. HINS, H. F. JELINEK, A. B. SHUCK, AND T. A. STEELE*)

Several hundred plate-type plutonium fuel elements are required to determine the effects of increasing percentages of ²⁴⁰Pu, ²⁴¹Pu, and ²⁴²Pu on reactor kinetics. The elements required are of the type shown by Figure 78. They consist of Pu-1.1w/oAl alloy plate core sealed in tight-fitting stainless steel jackets. It is

* Industrial Hygiene and Safety Division.

TABLE 42. REPRESENTATIVE MATERIAL BALANCE BASED UPON 10,000 GRAMS CHARGED

		ALLOY TO CORES SAMPLES & REMELT	ALLOY TO RECOVERY	PLUTONIUM	ASSUMED Pu LOSS @ 80% RECOVERY
PLUTONIUM 2,821	BINARY ALLOY 7,179	10,000		2,821	
10,000					
CASTING					
Skulls & Residues					
372			372	105	21.0
Loss by Difference					
5					0.2
Cast Bars					
9,623					
MACHINING					
Mill Cuttings					
308			308	87	17.4
Analysis Samples					
9		1,709 9			
Core Plates					
7,597					
CLEANING & INSPECTION					
Residue					
20			20	5.8	0.6
Core Plates					
7,577		7,577			
JACKETING					
Recovery of Usable Binary Alloy		9,295			
Alloy to Residue Recovery			700		
Plutonium to Residue Recovery				198	
Assumed Plutonium Loss					39.2

planned to manufacture such elements in isotopic ranges from 95w/o ^{239}Pu to 96w/o (^{240}Pu + ^{241}Pu + ^{242}Pu) as such materials become available. This program will also provide valuable information on the gamma and neutron-radiation levels experienced during the fabrication of plutonium from highly irradiated fuel, an important subject to the long-range power reactor program.

The immediate need was to fabricate 23 kg of plutonium with an average isotopic composition of 72.73% ^{239}Pu , 22.09% ^{240}Pu , 4.51% ^{241}Pu , and 0.64% ^{242}Pu

into plates and to jacket them. The plates are of three sizes. Each is 2.25 mm-thick and 45.0 mm-wide, but its length may be either 23.0 mm, 49.3 mm, or 74.7 mm. The number of plates of each length fabricated and jacketed during the year is 40, 70, and 96 respectively.

(1) Fabrication Process

The flow diagram of the process developed for fabricating these elements is shown in Figure 79. Most operations involving exposed plutonium were performed in helium-atmosphere gloveboxes in Building 350. The

350-876

FIG. 78. ZPR Fuel Element and Components. Pu-1.1w/oAl core with 22% ^{240}Pu , 4.5% ^{241}Pu and 0.6% ^{242}Pu isotopic composition.

raw materials to the process were plutonium buttons and aluminum wire. The product was stainless steel clad plutonium-1.1w/o aluminum alloy plates.

(2) Billet Casting

The Pu-1.1w/oAl alloy cast readily. Practical alloying temperatures of 1000°C or less are sufficiently low to allow the use of yttria-coated magnesia or graphite crucibles. Yttria-coated graphite molds are excellent. The difference between the liquidus and solidus temperatures is about 40°C. The solidification shrinkage is low as is the high-temperature thermal shrinkage. Both factors tend to favor casting soundness.

The charge to a virgin melt consisted of one entire plutonium button plus sufficient electrical-grade aluminum wire to make a 1.1w/o aluminum alloy. Since the isotopic composition of the billet produced was assumed to be that of the button charged, isotopic analysis of the billet was unnecessary. Billets were analyzed for aluminum, carbon, oxygen, and minor elements. Eight remelts were also made and were analyzed for isotopic composition.

The charge was melted, alloyed, and cast in an induction-heated, vacuum furnace. Pieces of button were placed on the bottom of the crucible and a suitable length of aluminum wire on top. The charge was

melted, superheated to about 950°C, and bottom poured. The billet produced was 16 mm thick, 50 mm wide, and between 100 mm and 150 mm high.

(3) Secondary Working

The billets were heated to between 350 and 400°C and rolled between 125 mm diameter by 200 mm rolls electrically heated to 325°C. Billet thickness was reduced from 16 mm to 0.6 mm in six passes of approximately 15% reduction each. The rolled bar, which was about 460 mm long, was cooled and sheared into three sections of equal length. Each section was returned to the mill and reduced to a thickness of 2.3 mm under these same conditions.

Final rolling was carried out at room temperature. The strips were reduced from 2.3 mm to between 2.29 and 2.25 mm. The close thickness control was required to meet a weight tolerance of $\pm 0.5\%$. Although the cold reduction was quite small, the alloy work hardened appreciably and tended to bow. It was straightened by heating it to 500°C between steel flats. A half-inch thick piece of steel equal in area to the workpiece furnishes all the pressure required in straightening.

Core plates were cut from the rolled strip with blanking dies. A force of 35 to 50 tonnes was required depending on the size of the core being blanked. Ethyl

FIG. 79. Flow Diagram-Manufacture of ZPR Reactivity Coefficient Elements.

FIG. 80. Fuel Element Assembly.

alcohol was used as a lubricant. The blanks produced were deburred and inspected. Each was (1) passed through a go, no-go gage to inspect its dimensions, (2) passed between parallel planes to measure its bow, and (3) weighed. Holes were punched in the overweight cores to bring them within the specified weight range.

(4) Element Assembly and Inspection

The completed core plates were cleaned and weighed just before they were loaded into jackets. The cores were power brushed under alcohol to remove non-adherent particulate matter. They were dried, weighed to the nearest 0.01 grams, and transferred to an uncontaminated glovebox for loading.

The stainless steel jacket subassemblies were inspected and an identifying number was electroetched on their surface. Each jacket subassembly consisted of (1) a length of rectangular tubing formed from sheet metal and closed by welding, and (2) a bottom end plug machined from square wire. This subassembly plus a top end plug and a spring constituted a fuel-element jacket.

The steps in element assembly are illustrated in Figure 80. A part of the welding fixture served as an assembly fixture. Four to six jacket subassemblies were placed in the fixture and fitted with loading funnels. The funnels prevented the core from contacting and contaminating the edges of the jacket subassembly during loading. The core plate and spring were loaded,

the funnel was removed, and the end plug was inserted. If the surfaces to be welded were clean, as judged by the counting of wipes, the assembly was moved into the welding chamber.

The upper end plug was welded to the jacket tube by means of a tungsten-electrode, DC arc welding process. The jackets were held between copper chills. The two shorter sides were hand welded and the two longer sides were welded semiautomatically. Before the final welding pass the weld chamber was sealed and an atmosphere of $\frac{1}{2}$ to $\frac{1}{3}$ standard atmosphere of 85 v/o helium–15 v/o argon gas was established.

The completed elements were checked for loose contamination and, if clean, taken from the glovebox system. Outside they were again checked for loose contamination by wipe counting and put in a total surface counter and checked for fixed contamination. The maximum allowable contamination is 10 disintegrations per minute loose and 500 disintegrations per minute fixed. Those elements found acceptable were leak detected, measured, and weighed to complete the process.

(5) Process Development

The average ^{241}Pu content of the buttons received was 4.51 a/o. ^{241}Pu is the source of a considerable amount of penetrating radiation. It decays by beta emission with a half-life of 13.2 years to ^{241}Am , a gamma emitter having a half-life of 458 years. The surface dose rate from this alloy was 5.5r/hr of com-

Fig. 81. Combination Blanking-Coining Dies for ZPR Fuel Cores.

350-873

bined beta and gamma radiation at the time fabrication began and increasing with time. The recommended exposure limit to hands is 1.5 r/week; therefore, a man can handle this material safely for only 15 minutes per week without leaded gloves.

The choice between fabricating techniques was influenced by the amount of hand processing that each required. Billet casting was preferred over precision casting because it required less inspection and sampling, both of which normally require the workpiece to be handled. Blanking was chosen as a secondary working process because it yields a core plate that requires a minimum of finishing. One of the die sets used is shown in Figure 81 to be upside down in that the punch is attached to the lower, stationary die shoe while the die is attached to the upper, movable shoe. The blanks, which normally stick in the die cavity, were carried up with the die and dropped out on top of the stock where they could easily be picked up with tongs.

Power scrubbing proved an excellent method of removing particulate material from core plates, and was done in a 152 mm-diameter, flat bottom metal dish. A dirty core plate was placed in the dish along with a steel disk containing a core-plate-size hole. The purpose of the disk was to take up space and allow the core

plate to be covered with a minimum amount of alcohol. The use of the disk rather than a smaller cavity in the disk bottom simplified cleanup. The scrubbing tool was a cup-type steel brush. Its bristles were parallel to its shank by which it was mounted in a portable drill press. All power scrubbing was performed in a nitrogen-atmosphere glovebox. After scrubbing, the core plates were thoroughly dried, but there was still concern that residual alcohol might be absorbed in porosity in the cores.

Three large elements that have been cleaned by this method have been heated to 93°C and maintained there for six hours. If there is an appreciable amount of alcohol in the elements, some expansion of the jacket should occur. To date no expansion has been observed.

The technique of loading core plates through a funnel was developed to prevent contamination of the jacket during loading. The funnels were made from 0.13 mm-thick aluminum foil. They were formed in three steps: (1) a strip was blanked from foil, (2) the ends of the strip were joined by spot welding to form a flattened hoop, and (3) the hoop was formed into a funnel by means of a rubber punch and a steel die. This type of forming technique does not harden the aluminum significantly. Funnels made from foil less

TABLE 43. EXPANSION CHARACTERISTICS OF U-25w/oPu-2.5w/oMo ALLOY

	As-Rolled		As-Cast
	Rolling direction	Transverse direction	
Mean coef. of exp., $\times 10^6/^{\circ}\text{C}$ 25 to 200	14.2	15.3	15.4
Mean coef. of exp., $\times 10^6/^{\circ}\text{C}$ 200 to transformation	25.5	24.8	26.2
Transformation range, $^{\circ}\text{C}$	545-620	545-620	540-630
Expansion, Δl	0.41%	0.41%	0.46%
Mean coef. of exp., $\times 10^6/^{\circ}\text{C}$ Transformation to 780	23.7	24.2	25.3

than 0.13 mm thick lacked sufficient strength to survive handling. Thicker foils are stronger but require larger core-to-jacket clearances. Impact extrusion is being considered as a way of making thinner, harder aluminum funnels.

c. PROPERTIES OF ZERO-POWER URANIUM-PLUTONIUM METAL FUELS (H. V. RHUDE)

Density, strength, ductility, fabricability, specific heat, thermal-expansion characteristics and air-corrosion resistance at room temperature were studied on three groups of uranium-plutonium-based alloys of interest for zero-power reactors.

The alloy finally selected for use in the Zero-Power Plutonium Reactor (ZPPR) has a nominal composition of U-28w/oPu-2.5w/oMo.

Because of the great concern for the pyrophoric nature of U-Pu alloys, air-corrosion resistance was one of the main considerations used in picking a suitable alloy. Air-corrosion tests that were started in 1964 and 1965 on a range of U-Pu-Ti, U-Pu-Zr, and U-Pu-Mo alloys were terminated in 1966.

The U-20w/oPu-2.5w/oMo alloy developed for the Southwest Experimental Fast Oxide Reactor (SEFOR) fast critical experiment⁽³⁶⁾ had the best corrosion resistance of all the uranium-plutonium alloys tested. Larger amounts of plutonium, however, were required for ZPPR, so alloys in the range of U-25w/oPu-2.5w/oMo to U-30w/oPu-2.5w/oMo were studied. The increased amount of plutonium decreased the air-corrosion resistance. In one series of air-corrosion tests the first signs of deterioration appeared after five months instead of after eight months as for the SEFOR alloy. In another test, however, a similar alloy did not begin to deteriorate until after 21 months.

⁽³⁶⁾ Kelman, L. R., Rhude, H. V., and Savage, H., *Development of a Metal Fuel for SEFOR Fast Critical Experiments and for ZPPR*, Trans. ANS, 7(2), November 1964, 401.

Earlier observations suggested that this variation in air-corrosion resistance might be related to the carbon content. Air-corrosion tests were made on U-Pu-Mo alloys with carbon contents of 190 to 2300 ppm carbon. The initial formation of surface flakes on these alloys indicated that the alloys with the lower carbon were more corrosion resistant, but after 15 months of testing, the alloy with the highest carbon content is still solid, while all the others are in various stages of cracking and disintegration, with the lower carbon alloys being completely crumbled.

In an air-corrosion test of two SEFOR fuel plates manufactured by NUMEC, the plate with 1800 ppm carbon held up better than one with 1200 ppm carbon.

From these two series of tests it appears that carbon in the range of 1500 to 2300 ppm carbon has a beneficial effect upon the air-corrosion resistance of the U-Pu-Mo alloys. Before a definite conclusion can be drawn, however, further tests are needed; and other factors must be studied, such as the effect of grain size.

Some consideration has been given to the possibility of rolling the fuel plates for ZPPR. To determine whether or not rolling would produce anisotropic expansion characteristics in the U-Pu-Mo alloys, a casting of U-25w/oPu-2.5w/oMo alloy was hot rolled at 650°C to 50% reduction, then machined into dilatometer specimens parallel and transverse to the rolling direction. The material was extremely brittle and broke repeatedly when attempts were made to turn specimens on a lathe. Dilatometer specimens were finally cut on an Elox machine (by electrical discharge cutting), and only a final, very light cut taken on the lathe.

The expansion characteristics are virtually the same in both the rolling and transverse directions. The data are given in Table 43 along with those of the as-cast alloy.

Compatibility tests were run on U-25w/oPu-2.5w/oMo and U-28w/oPu-2.5w/oMo against 304-L stainless steel, at 600, 650 and 700°C, for one week. In both alloys there was a slight reaction between the specimen and stainless steel at 600°C (120 μ penetration of stainless steel into fuel, 15 to 20 μ reaction layer of fuel into stainless steel). At 650°C the stainless steel penetration into the fuel was much more severe, and at 700°C alloying and melting occurred.

d. FLUX PERTURBATION ELEMENTS (N. J. CARSON, A. CARR, A. G. HINS, AND D. C. CARPENTER)

Eleven elements were manufactured during the past year for studies of the perturbation of zero-power reactor neutron flux by fuel containing the higher plutonium isotopes. Each element consisted of a Pu-

1.2w/oAl alloy core inside a cylindrical stainless steel jacket. A typical element is shown in Figure 82. The outside dimensions of these elements were 10.7 mm in diameter by 50.8 mm long.

The jacket cylinders were loaded with two types of plutonium cores: (1) solid cylinders and (2) split tubes of "napkin rings." The cylindrical cores were either 5.1, 2.5, or 1.6 mm in diameter. They were supported on the axial centerline of the element. The napkin rings were formed from 0.50, 0.25, and 0.13 mm-thick foils. The napkin rings were intended to be in contact with the jacket wall. All cores, but the smallest cylindrical core, were made in duplicate. One set was made with plutonium containing 4.5% ^{240}Pu and the other with plutonium containing 22% ^{240}Pu . The smallest cylinder was made with the higher ^{240}Pu content.

The plutonium-1.1w/o aluminum alloy was made and cast in an induction-heated vacuum furnace. The cast billet was rolled at 350°C to 400°C between rolls heated to 325°C. The rolled foils were sheared and roll-

formed to make the napkin-ring cores. The cylinders were turned from pieces sheared off as reduction proceeded. The smallest cylinder was made by first turning a 4.7 mm-diameter cylinder and then plunge cutting this to 1.6 mm in diameter in a single pass.

In order to achieve contact with the jacket, the napkin rings were rolled to a free diameter that was larger than the jacket bores. They were compressed to the jacket-bore diameter by loading them through metal funnels. The funnels and jackets were held in soft plastic fittings on a gloveport pouch. This allowed the loaded jacket and plastic fitting to be sealed from the loading glovebox and transported to the welding glovebox line. Difficulty was experienced in rolling the plutonium foils into a shape that would compress to a true cylinder, and in keeping contaminating oxide out of the interface between the funnel and jacket. Several of the specimens were made over because of either poor core fit or contaminated welds.

FIG. 82 Flux Perturbation Specimen and Components with Napkin ring Core

7. EBR-II Assistance

a. SORET EFFECT IN THE BISMUTH-TIN EUTECTIC ALLOY (T. F. KASSNER AND D. L. RINK)

The following study has been initiated as part of a program to provide basic information concerning metallurgical factors that may affect the operation of the rotating plug seals in EBR-II. Two phenomena are considered to be among the primary causes of plug rotation difficulties. Temperature gradients within the liquid alloy provide a condition in which a phase of solid bismuth can grow in low-temperature regions in the seal by a thermal diffusion process. The solid bismuth exhibits a relatively high melting temperature compared to normal seal operating temperatures and could inhibit plug rotation until dissolved through a sufficiently long heating period in the "molten" mode of operation. Secondly, oxidation of the liquid alloy by impurities in the nitrogen cover gas results in an accumulation of oxide in the outer annulus of the seal.

The important cross-phenomenon arising from the coupling of heat conduction and diffusion in condensed phases is the Soret effect. Winter and Drickamer⁽³⁷⁾ have reported that bismuth preferentially diffuses to the cold end of a couple having an initial composition of 50w/oBi-50w/oSn under a temperature gradient of 50°C over 1.27 cm at an average temperature of 295°C. Another necessary condition for the growth of a bismuth phase from a solution in a temperature gradient is that the diffusion path through the liquid must intersect the bismuth liquidus phase boundary on the bismuth-tin phase diagram.

(1) Experimental

Thermal diffusion measurements are being made on an alloy with a composition of 57.2w/oBi and 42.8w/oSn. The diffusion cell consists of a 304 stainless steel tube 2.90 cm long, 0.28 cm ID, and 0.38 cm OD. Six thermocouples are spot-welded to positions along the length of the tube. A linear temperature gradient is imposed by means of a rod heater imbedded in a nickel-plated copper block. By varying the heater current and the air cooling to a similar block on the opposite end of the cell, almost any mean temperature and ΔT can be obtained.

The temperature profile in Figure 83 was obtained for a couple for which further data will be presented. A dynamic vacuum was maintained around the diffusion cell during the run to minimize heat loss through the tube wall. The run was concluded by quenching the sample with a helium gas flow. The sample was then

sectioned and mounted along with a series of bismuth-tin standards for electron-microprobe and metallographic analysis.

(2) Results

Figures 84a to d show photomicrographs at four positions along the length of the couple. For this run the cold end of the liquid was fixed by the eutectic temperature of the alloy (139°C). The solid eutectic-bismuth interface and the bismuth-liquid interface are shown in Figures 84d and 84c, respectively. A region at a distance of 3 mm from the bismuth layer and at the hot end of the couple, Figures 84b and 84a, respectively, show that the tin concentration increases at the hot end of the couple.

Electron-microprobe data from BiL_α radiation obtained at positions along the length of the couple were used with the calibration curve in Figure 85 to determine the plot of concentration versus distance in Figure 86. The validity of the microprobe data can be checked by setting up the mass balance for bismuth in Equation (1),

$$\int_{X_0}^{X_2} \rho_{(x)}^i C_0 dx - \int_{X_0}^{X_1} \rho_{(x)}^f C_{(x)} dx = 100\rho_{\text{Bi}}(X_2 - X_1) \quad (1)$$

where

$C_0 = 57.2\text{w/o Bi}$, the initial bismuth concentration in the liquid

$C_{(x)} = 0.2727X + 51.77$, the final concentration profile in the liquid from Figure 86

$\rho_{\text{Bi}} = 9.736 \text{ gm/cm}^3$ at 157°C, based on data from the Handbook of Chemistry and Physics⁽³⁸⁾

$\rho_{(x)}^i$ is the initial density profile when the temperature gradient is applied (no diffusion has occurred).

$\rho_{(x)}^f$ is the final density profile after the stationary state has been attained.

X_0 , X_1 , and X_2 are positions along the couple in mm measured from the hot end, (see Figure 86)

Sauerwald and Töpler⁽³⁹⁾ have measured the density of a number of Bi-Sn alloy compositions as a function of temperature. Their data can be used with Equation (2):

⁽³⁸⁾ *Handbook of Chemistry and Physics*, Chemical Rubber Publishing Co., Cleveland, Ohio, 40th Ed., 1958-59, p. 201.

⁽³⁹⁾ Sauerwald, F. and Töpler, K., *Zeitschrift für anorganische und allgemeine Chemie*, **157** (1926), pp. 117-137.

⁽³⁷⁾ Winter, F. R. and Drickamer, H. G., *J. Phys. Chem.*, **59** (1955), pp. 1229-30.

FIG. 83. Temperature Profile for the Diffusion Couple.

$$d\rho_{(T,C)} = \left(\frac{\partial \rho}{\partial T}\right)_C dT + \left(\frac{\partial \rho}{\partial C}\right)_T dC \quad (2)$$

to obtain the density of any alloy composition at a temperature of interest from Equation (3)

$$\rho_{C_{B1} w/o}^{T^\circ C} = 8.62 + 2.84 \times 10^{-2} [C_{B1} - 58.0] - 9.38 \times 10^{-4} [T - 200] \quad (3)$$

By selecting a temperature from Figure 83 and a composition from Figure 86 at the same distance coordinate, the density of the alloy at that position can be determined from Equation (3). This method was used to obtain the initial and final density distributions in Equations (4) and (5), respectively.

$$\rho_{(x)}^i = 9.40 \times 10^{-3} X + 8.462 \quad (4)$$

$$\rho_{(x)}^f = 1.72 \times 10^{-2} X + 8.286 \quad (5)$$

After substituting the relations for ρ_{B1} , $\rho_{(x)}^i$, $\rho_{(x)}^f$, $C_{(x)}$, and C_0 into Equation (1) and integrating between the limits, we obtain:

$$\begin{aligned} & [0.269 (X_2^2 - X_0^2) + 484.0 (X_2 - X_0)] \\ & - [1.563 \times 10^{-3} (X_1^3 - X_0^3) + 1.575 (X_1^2 - X_0^2) \\ & - 429.0 (X_1 - X_0)] = 973.6 [X_2 - X_1] \end{aligned} \quad (6)$$

Values of $X_0 = 1.0$ mm and $X_2 = 22.9$ mm, which were determined from the sample, were substituted into Equation (6) and a trial-and-error method of solution

was used to obtain a value of $X_1 = 21.85$ mm. This value of X_1 gives a layer thickness ($X_2 - X_1$) of 1.05 mm compared to a measured value of 1.10 mm.

DeGroot⁽⁴⁰⁾ gives the following flux equation for uni-dimensional thermal diffusion in a binary system,

$$J_1 = -J_2 = -\rho D \left[\frac{dC_1}{dX} + \frac{\alpha C_1(1 - C_1)}{T} \left(\frac{dT}{dX} \right) \right] \quad (7)$$

where

J_1, J_2 = flux of component (1) and (2), respectively

D = chemical diffusion coefficient

ρ = average density of the alloy

C_1 = mass fraction of component (1)

T = absolute temperature

α = thermal diffusion factor

The thermal diffusion separation in a binary alloy can be examined in terms of the stationary state (i.e., $J_1 = -J_2 = 0, J_q \neq 0$) solution to Equation (7).

$$\int_{C_{cold}}^{C_{hot}} \frac{dC_1}{C_1(1 - C_1)} = \alpha \int_{T_{cold}}^{T_{hot}} \frac{dT}{T} \quad (8)$$

Integration of Equation (8) gives,

$$\ln \left(\frac{1 - C_1}{C_1} \right)_{hot} \left(\frac{C_1}{1 - C_1} \right)_{cold} = \alpha \ln \frac{T_{hot}}{T_{cold}} \quad (9)$$

If we designate bismuth as component (1) and tin

⁽⁴⁰⁾ DeGroot, S. R., *Thermodynamics of Irreversible Processes*, Interscience Publishers Inc., New York, 1951, p. 114

Tin Dendrite Formations

45775

FIG. 84a.

250X

FIG. 84. Photomicrographs at Four Positions along the Length of a Longitudinal Section of the Diffusion Couple; (a) Near the hot end of the couple; (b) About 3 mm to the Left of the Bismuth Bar (see Figure 36); (c) the Liquid-bismuth Interface; (d) the Bismuth-solid Eutectic Interface. Etchant: 5% ammonium per sulfate solution.

as component (2), the values of $(C_1 = 0.525, T = 611^\circ\text{K})_{\text{hot}}$ and $(C_1 = 0.575, T = 430^\circ\text{K})_{\text{cold}}$ can be obtained from Figures 83 and 86. These values when substituted into Equation (9) give a value for the thermal diffusion factor, α , of 0.58.

Further experiments will be made to determine α as a function of composition and then the results will be used to predict the maximum bismuth layer thickness for given temperature gradients and average temperatures.

Tin Dendrite Formations

45774

FIG. 84b.

250×

b. IRRADIATION-INDUCED CHANGES IN MECHANICAL PROPERTIES OF EBR-II FUEL JACKETS (W. F. MURPHY)

A surveillance program on EBR-II Mark I type of fuel elements resulted in a large number of Type 304L stainless steel tubular fuel jackets becoming available for tube-burst tests at various temperatures. The principal parts of the fuel element are shown in Figure 87.

During irradiation the fuel elements were immersed in flowing sodium containing 10 to 15 ppm of oxygen. Therefore, the jackets were in contact with flowing sodium on the outside and helium, static sodium and fuel on the inside. The temperature of the sodium entering the reactor core was 370°C and, for the jackets used in these tests, the exit temperature of the sodium has been calculated as 497°C for Row 3 and 517°C

Bismuth

45773

FIG. 84c.

250×

for Row 4. All jackets tested thus far were from sub-assemblies in Rows 3 and 4. The increase in temperature along the jacket is given in Figure 88 for Row 4. The axial flux distribution at the center of the reactor for 45 Mw operation is related to the jacket as in Figure 88. The neutron flux to which the jackets used in the burst tests were exposed would be somewhat less than shown in the figure. The maximum fast neutron exposure was $1.4 \times 10^{22} \text{ n/cm}^2$.

The irradiated fuel rods were taken apart in the nitrogen cell of the Alpha-Gamma Cave. A dry abrasive cut-off wheel was used to open the fuel elements and section the jackets. Usually cuts into the fuel were avoided to reduce contamination. After the opening of the fuel element, it was put into a furnace and heated to 200°C. With the sodium molten the fuel pin could be removed. In some early tests, before the pattern of strength variation along the length of the jacket was

45772

FIG. 84d.

250×

recognized, the whole tube was used as a specimen. In these cases thorough removal of the sodium was not possible. Later when shorter (3 to 3.5 inches) burst specimens were chosen for routine testing, they were cleaned ultrasonically in ethyl alcohol.

The unirradiated control specimens were full-length tubes with bottom end plugs and spacer wires attached. The Type 304L stainless steel was in the annealed condition.

Tube-burst tests have been made over a range of temperatures from 25° to 1000°C in a three-zone vertical furnace. The tests were made in a slowly flowing inert gas atmosphere, either helium or argon, inside a stainless steel chamber in the furnace. A thermocouple well was provided so that the temperature profile along the length of the specimen could be determined with a Chromel-Alumel thermocouple.

Compression-type fittings were used on the specimen.

106-9241

FIG. 85. Counting Rate for Bismuth L_{α} Radiation vs Composition of Bi-Sn Alloy Standards.

Pressure was applied directly to the specimen by a high-pressure diaphragm type pump. The rate of load application was determined by the pump and loading was in pulses. The use of gas (helium or argon) as the pressurizing medium resulted in appreciable stored energy, which was partly expended in fragmenting the specimens on rupture.

Pressures were indicated on a gauge outside the hot cell. The bursting pressure (psi) as read from the dial gauge was converted to rupture strength in psi by use of the equation for thick-walled tubes.

$$\sigma_t = P \cdot \frac{K^2 + 1}{K^2 - 1}$$

where

σ_t = tangential stress, inner surface

P = pressure

K = (OD/ID)

After the burst test, diameter measurements were made along the length of the specimen with a micrometer. Reliable readings could not be made near the place of rupture because of irregularities resulting from the tearing action of the expanding gas.

Rupture strengths along the lengths of fuel jackets are shown in Figure 89 for test temperatures of 25°, 400°, 500°, 600°, 700°, 800°, 900°, and 1000°C. For each test temperature, except 500°C, the plotted data refer to tests on one fuel jacket. The curve for the 500°C tests represents data from several jackets. The temperature of the jacket in the reactor and fast flux exposure with reference to position along the length of the jacket

106-9242

FIG. 86. Concentration vs Distance Plot for the Diffusion Couple.

Fig. 87. EBR-II Fuel Element.

are also indicated in Figure 89. Along the lower sections of the jacket used for the 25°C test the strength exceeded the capacity of the equipment and these sections could not be broken. Test temperatures of 800°C, 900°C, and 1000°C have apparently resulted in complete annealing out of strength variations along the length of the jackets. At test temperatures of 700°C and below there is a tendency for the strength of the jackets to be greatest near or below the reactor midplane and for the minimum strength to be at the top of the jacket. The strength as indicated by these biaxial stress tests is related to the flux, the temperature, and time.

In Figure 90 rupture strength as given in Figure 89, is plotted against test temperature. Data from unirradiated specimens are compared with those from irradiated specimens for two positions along the jacket—at the reactor midplane and near the top of the fuel column. The rupture strengths of the irradiated specimens at the reactor midplane are consistently greater than near the top of the fuel column up to 800°C. From 800°C to 1000°C the rupture strengths are the same for the two positions. The irradiated specimens are stronger than the controls below 700°C. Between 700°C and 800°C the graph for the irradiated specimens crosses that for the control specimens. At 800°C, 900°, and 1000°C the irradiated specimens consistently exhibit less strength than the unirradiated control specimens.

The percent change in diameter for unirradiated and irradiated specimens is shown in Figure 91. There seems to be a minimum in the ductility of both the irradiated and unirradiated specimens at about 400 to 500°C. In this temperature range the irradiated specimens show about 1% or less diametral increase. At room temperature and above 600°C the ductility of the irradiated specimens is better than at 400° to 500°C. The diameter increases for the unirradiated specimens ranged from 9 to 26% over the range of test temperatures. The fractures were ductile for both the unirradiated and irradiated specimens at all test temperatures.

Fig. 88. Fuel Cladding with Reference to Reactor Operating Conditions

The maximum loss of ductility occurs at test temperatures over just the span encountered by the jackets while in the reactor. While increasing the test temperature up to 1000°C results in greater ductility, it is still much less than for unirradiated Type 304L tubes.

The principal cause of the property changes noted in these specimens is atomic displacements, which

FIG. 89. Rupture Strength along Length of Fuel Jacket.

FIG. 90. Rupture Strength vs Test Temperature for EBR-II Fuel Jacketing (Type 304L Stainless Steel).

result in point defects and defect clusters, dislocations, etc. While in the reactor, annealing processes are occurring concurrently with the atomic displacements and the net result is determined by the neutron flux and temperature. Helium, which results from (n, α) reactions involving iron, chromium, nickel, and other elements in fast reactors, is not expected to be a factor in property changes of Type 304L tubes in the EBR-II

106-9214

FIG. 91. $\Delta D/D\%$ of Type 304L Stainless Steel Jacketing for EBR-II Fuel vs Test Temperature.

because of the low temperatures. It is probable that the lower strength and low ductility of the irradiated specimens compared to the unirradiated at test temperatures of 800°, 900°, and 1000°C are associated with helium from (n, α) reactions.

c. ANOMALOUS SWELLING OF MARK IA FUEL (F. G. FOOTE)

(1) EBR-II Driver Fuel—Mark I Series

The EBR-II fuel element consists of a cast pin of U-5w/oF alloy loosely jacketed in a sealed stainless

(ALL DIMENSIONS IN MM)

106-9295

FIG. 92. EBR-II Mark I Fuel Element.

steel tube with a heat transfer bond of sodium in the annulus between the fuel pin and jacket and overlaying the fuel pin to assure submergence. A restrainer built into the top of the fuel element restricts axial growth of the fuel pin and a gas plenum exists above the sodium. This is a well-defined mechanical system and it can be analyzed in terms of the amount of fuel swelling permitted by the various restraints in the system. If, in addition, there is an empirically determined swelling-burnup curve, one can estimate the burnup to which the configuration can be taken.

(2) The Mark I Fuel Element

Figure 92 is a dimensioned drawing of the EBR-II Mark I fuel element. Figure 93 is a schematic drawing showing the quantities used in the calculations. The restrainer is not shown in Figure 93. It is sufficient to know that the axial growth of the fuel pin can be limited to some definite amount (G), the distance between the top of the fuel pin and the bottom of the restrainer. We will use as reference, the geometry of Figure 92,

(Mark I) operating at 45 Mw. The numerical values used in the calculations are given in Table 44.

From the dimensions given in Table 44 we obtain the following geometric quantities used in the calculations.

- (1) A measure of the possible radial swelling and also of the amount of bonding sodium in the annulus between fuel pin and jacket: (D_i/D_f) .
- (2) The gas plenum volume referred to the fuel pin volume:

$$X = (V_g/V_f) \times 100$$

- (3) The axial restraint:

$$Z = (G/L_f) \times 100$$

- (4) A measure of the amount of sodium overlay; i.e., the amount of sodium above the top of the fuel pin. L_n is defined by volume of sodium in the overlay = $(\pi/4)D_i^2 L_n$

$$1 + (L_n/L_f)$$

FIG. 93. Initial Geometry: Cold.

From the temperatures and expansion coefficients in Table 45, we obtain:

$$\text{Fuel: } A = 1 + \alpha_f (T_f - T_0)$$

$$\text{Jacket: } B = 1 + \alpha_j (T_j - T_0)$$

$$\text{Sodium: } C = 1 + \alpha_n (T_n - T_0)$$

The derived quantities, along with certain temperatures, and the initial gas plenum pressure are tabulated in Table 45.

(3) Mechanical Restraint

The amount of fuel swelling (Y) can be limited by mechanical restraints built into the design. The radial swelling cannot exceed the inside diameter of the fuel jacket without producing jacket strain and the axial swelling is limited by the restrainer built into the fuel element. We can then write:

$$Y = (100 + Z) (B/A)^2 (D_j/D_f)^2 - 100 \quad (1)$$

where $Y = \% \Delta V/V =$ volume percent swelling of the fuel. Putting in the appropriate values of Table 45, we have:

if fuel swells to the jacket and to the restrainer:

$$(Z = 2.81\%): Y = 20.12\%$$

if fuel swells to the jacket and there is no axial swelling:

$$(Z = 0\%): Y = 16.84\%$$

(4) Pneumatic Restraint

A gas space (V_g) is built into the top of the fuel element. During welding closure of the element jacket, gas at more or less ambient temperature and pressure is sealed into this space. As the fuel element is heated to operating temperature, this trapped gas is heated and is also compressed by the expansion of bonding sodium. Further as the fuel swells due to the accumulation of fission products, sodium in the annulus is displaced and further compresses the gas.

TABLE 44. EBR-II FUEL ELEMENT DATA

	Mark I	Mark IA	Mark IB
<i>Fuel Pin</i>			
Diameter (D_f), (mm)	3.66	3.66	3.66
Length (L_f), (mm)	361.2	342.9	342.9
Volume (V_f), (mm ³)	3800	3608	3608
<i>Jacket</i>			
Outside Diameter (OD), (mm)	4.42	4.42	4.42
Inside Diameter (IR or d), (mm)	3.96	3.96	3.96
Inside Length (L_j), (mm)	439.4	439.4	439.4
Inside Volume (V_j), (mm ³)	5412	5412	5412
Gap (Axial Restraint) (G), (mm)	10.16	10.16	10.16
Equivalent Sodium Level (L_n), (mm)	13.85	13.85	9.15
Gas Volume, (mm ³)	501.7	665.8	931
<i>Pressure</i>			
Initial Gas (P_0), (kg/cm ²)	1.0	1.0	1.0
<i>Temperatures</i>			
Fuel (T_f)	825°	825°	825°
Jacket (T_j)	770°	770°	770°
Sodium (T_n)	770°	770°	770°
Gas Plenum (T_g)	770°	770°	770°
Room Temp. (T_0)	300°	300°	300°
<i>Expansion Coefficients</i>			
Fuel (U-5w/oFs) (α_f) (°C ⁻¹) (Linear)	$16.7 \cdot 10^{-6}$	$16.7 \cdot 10^{-6}$	$16.7 \cdot 10^{-6}$
Jacket (304 SS) (α_j) (°C ⁻¹) (Linear)	$18.4 \cdot 10^{-6}$	$18.4 \cdot 10^{-6}$	$18.4 \cdot 10^{-6}$
Sodium (α_n) (Volume)	$340.5 \cdot 10^{-6}$	$340.5 \cdot 10^{-6}$	$340.5 \cdot 10^{-6}$

The relationship between fuel swelling (Y) and the pressure in the gas space is given by:

$$P_g = \frac{\left[\left(\frac{1}{A^3} \right) \left(\frac{T_g}{T_0} \right) \cdot P_0 \right] \cdot X}{100 \left(\frac{C - A^3}{A^3} \right) + \left(\frac{B}{A} \right)^3 \cdot X - 100 \left(\frac{C - B^3}{A^3} \right) \left(\frac{D_i}{D_f} \right)^2 \left(1 + \frac{L_n}{L_f} \right) - Y} \quad (2)$$

Equation (2) makes no allowance for elastic or plastic deformation of the jacket nor for the compressibility of sodium.

Substituting appropriate values from Table 45 into equation (2), we have:

$$P_g = \frac{32.981}{10.019 - Y} \quad (\text{Mark I}) \quad (2a)$$

The calculated gas plenum pressure vs. fuel swelling is given in Figure 94 and tabulated in Table 46.

(5) Hoop Stress in Jacket

The maximum hoop stress in the jacket due to internal pressure is given by the thick-wall tube formula:

$$\sigma = \left(\frac{K^2 + 1}{K^2 - 1} \right) \cdot P_g \quad (3)$$

where $K = \text{OD/ID}$ of the jacket = $(4.42/3.96 = 1.116$ and hence $\sigma = 9.15 P_g$.

It should be noted that beyond 8 or 9% swelling of the fuel alloy the internal gas pressure and the hoop stress increase very rapidly and, if no jacket deformation is assumed, the pressure stress approaches infinity slightly beyond 10% swelling. It should be noted that the assumptions used to devise the curves in Figure 94 are pessimistic in several respects. Liquid sodium is compressible and at high temperature and pressures will occupy somewhat less volume than assumed in the calculations. We have also assumed that all parts of the fuel element are at the temperatures given in Table 45. Actually the lower end of the rod is at a lower temperature, the lower limit being set by the temperature of the inlet coolant (370°C). Hence, not all of the sodium is at the assumed temperature and the volume occupied by the hot sodium is less than that assumed in the calculations. However, these are second order effects and we have been inclined to use them as a safety factor to accommodate an occasional bad-acting fuel pin rather than to factor them into the design calculation. In any case, it seemed prudent to limit the burnup to such values as would produce fuel swellings of around 8% and to thus stay well below the steeply-rising part of the pressure-swelling curve.

Another concern has been the effect of a mild excursion in power upon the internal gas pressure. Repeating the calculations with all temperatures increased by 100°C gives $P_g = 36.716/8.862 - Y$. These

results are also tabulated in Table 46 and plotted in Figure 94. At swelling values below 8% the effect of

the assumed temperature excursion is relatively mild but at 9% swelling the pressure changes from 32 kg/cm² to infinity by thermal expansion effects alone. Again it appears prudent to keep the swelling of fuel at such values that a moderate increase in temperature will not produce large increases in internal gas pressure.

Finally, it should be noted that the mechanical restraints never operate over the entire length of the fuel pin. The calculation under "Mechanical Restraint" showed that with no axial growth, the fuel must swell 16.8% to completely fill the annulus and to be in contact with the jacket over its entire length. To completely fill the space below the restrainer, the fuel must swell 20.1%. Figure 94 shows that long before these amounts of swelling have occurred, the internal gas pressure has become infinitely large and the jacket has long since been ruptured. The effect comes about through the fact that the volume of sodium in the annulus (648 mm³) exceeds the volume of gas plenum (502 mm³).

(6) Mark IA Fuel Element

The observations noted above indicate that the allowable amount of fuel swelling and hence the achievable burnup of the Mark I fuel is pneumatically rather than mechanically limited. The Mark IA fuel design relaxes this pneumatic restraint to some extent although not completely. Two changes were made in the internal structure of the fuel rod: the length of the fuel pin was decreased to 342.9 mm (a decrease of 5%) and the stem of the restrainer increased in length by the same amount. The pertinent data are tabulated in

TABLE 45. DERIVED DATA USED IN CALCULATIONS

	Mark I	Mark IA	Mark IB
(D_i/D_f)	1.082	1.082	1.082
X (%)	13.20	18.45	25.81
Z (%)	2.81	2.96	2.96
$1 + L_n/L_f$	1.038	1.040	1.027
A	1.009	1.009	1.009
B	1.008	1.008	1.008
C	1.160	1.160	1.160
T_0 (°K)	300	300	300
T_g (°K)	770	770	770
P_0 (kg/cm ²)	1	1	1

FIG. 94. Calculated Gas Plenum Pressures.

Tables 44 and 45. The operating temperatures and expansion coefficients remain unchanged.

For the mechanical restraints, using equation (1)

$$\begin{aligned} \text{if } Z = 2.96 \text{ then } Y &= 20.30 \\ \text{and if } Z = 0.00 \text{ then } Y &= 16.84 \end{aligned}$$

and the mechanical restraints are almost identical with those of Mark I.

For the pneumatic restraint, from equation (2)

$$P = \frac{46.099}{15.222 - Y} \quad (\text{Mark IA})$$

These values of internal gas pressure (and hoop stress) for the Mark IA fuel are also tabulated in Table 46 and plotted on Figure 94. Clearly, to produce the same internal pressure, the Mark IA fuel can swell considerably more than the Mark I fuel.

(7) Fuel Swelling vs. Burnup

There is no very good way of estimating in advance the rate of swelling of a particular fuel under a particular set of operating conditions. Tests on specimens of different fuel materials will indicate which materials are better than others but it is often difficult to apply this information to an actual fuel element oper-

ating in a somewhat different environment. The swelling consists of at least two parts:

$$\frac{\% \Delta V}{\% \text{ Bu}} = \frac{Y}{\text{Bu}} = Y_s + Y_g$$

Y_s is the swelling, per unit burnup, due to the accumulation of solid fission product and for metallic fuels has a value of 2 to 3% per atom percent burnup. The second term (Y_g) is the swelling due to the accumulation of gaseous fission products as small bubbles within the fuel material. At 1% burnup and higher, the second term predominates and is a complicated function of the properties and structure of the fuel material, the operating conditions (temperature, thermal cycling, burnup rate, etc.), and the burnup itself.

Rather than attempt to evaluate these terms from the properties of the material and from test irradiations under different conditions, the EBR-II Fuel Surveillance Program empirically determines the swelling of EBR-II fuel pins under actual conditions in the core operating at 45 Mw. The method most used in determining the fuel swelling involves measuring the change in sodium level produced by swelling of the fuel. Thus:

$$Y = 25\pi \left[\frac{D_j - D_s}{V_f} \right] [F - F_0] \quad (4)$$

where

- D_j = inside diameter of fuel jacket
- D_s = diameter of restrainer stem
- V_f = preirradiation volume of fuel pin
- F_0 = preirradiation sodium level
- F = postirradiation sodium level

We have then a nondestructive method of measuring fuel swelling.

(8) Behavior of Mark I Fuel

A plot of fuel swelling, determined by the sodium level method, as a function of average burnup in EBR-II operating at 45 Mw, is shown in Figure 95 as open circles. This gives us an average swelling of 6 to 7% at a burnup of 1%.

Reference to Figure 95 shows that, with this amount of fuel swelling, the internal gas pressure is approximately 10 kg/cm² at operating temperatures and would not exceed 20 kg/cm² in case of a 100°C temperature excursion. Another 0.1% burnup (another 5 days operation) would produce swellings in excess of 8% and we would then be close to or at the rapidly rising part of the pressure-swelling curve. Further the spread in swelling values within a given fuel element is rather large, average values only are plotted on Figure 95. The highest value of swelling, calculated

TABLE 46. CALCULATED INTERNAL GAS PLENUM PRESSURES AND HOOP STRESSES IN JACKET

% Swelling of Fuel (Y)	Internal Gas Pressure (P) (kg/cm ²)				Jacket Hoop Stress (σ) (kg/cm ²)			
	Mark I + 100°C	Mark I	Mark IA	Mark IB	Mark I + 100°C	Mark I	Mark IA	Mark IB
0	4.1	3.3	3.0	2.8	38	30	27	26
2	5.4	4.1	3.5	3.1	49	38	32	28
4	7.6	5.5	4.1	3.4	70	50	38	31
6	12.8	8.2	5.0	3.8	117	75	46	35
7	19.7	10.9	5.6	4.1	180	100	51	38
7.5	27.0	13.1	6.0	4.2	247	120	55	38
8	42.6	16.3	6.4	4.4	390	149	59	40
8.25	60.0	18.6	6.6	4.4	549	170	60	40
8.5	101.4	21.7	6.9	4.5	928	199	63	41
8.6	140.1	23.2	7.0	4.6	1282	212	64	42
8.7	226.6	25.0	7.1	4.6	2073	229	65	42
8.8	592.2	27.1	7.2	4.6	5419	248	66	42
9	∞	32.4	7.4	4.7	∞	296	68	43
9.5		63.5	8.1	4.9		581	74	45
9.8		150.6				1378		
9.85		195.2				1786		
9.9		277.2				2536		
10		∞	8.8	5.0		∞	81	46
11			10.9	5.5			100	50
12			14.3	6.0			131	55
13			20.7	6.6			189	60
14			37.7	7.3			345	67
14.5			63.8	7.8			584	71
14.8			109.2	8.1			999	74
14.9			143.2	8.2			1310	75
15			207.7	8.3			1900	76
15.1			377.9	8.4			3458	77
16			∞	9.5			∞	87
16.84				10.9				
(Z = 0)								
18				13.5				124
20				23.2				212
20.30				26.0				238
(Z = 2.96)								
(21)				(36.2)				(331)
(22)				(82.6)				(756)
(22.5)				(229.7)				(2102)
(22.6)				(356.5)				(3262)
(22.78)				(∞)				(∞)

from the sodium level measurements, was 8.7% but part of this could have been due to a higher than average value of F_0 . There is considerable scatter in the data but the equation

$$Y = 6.80 \cdot \text{Bu}^2 \quad (5)$$

fits the observations reasonably well and is weighted to favor the upper part of the scatter band. Equation (5) establishes a burnup scale which is plotted at the top of Figure 94. We have then several different scales associated with Figure 94. It is convenient to replot Figure 94 in terms of jacket hoop stress as a function of fuel burnup and this has been done in Figure 96. It must be emphasized, however, that Figure

96 is valid only for a particular swelling behavior, that is, $Y = 6.80 \text{ Bu}^2$. A different swelling-burnup relationship would yield a different scale at the top of Figure 94 and would change the position of the curves as plotted on Figure 96.

(9) Behavior of Mark IA Fuel

As indicated earlier, the intention in the Mark IA fuel element design was to increase the gas volume/fuel volume ratio so that we could allow larger amounts of fuel swelling while still keeping the internal gas pressure within reasonable limits. Reference to Figure 94 shows that if we can tolerate an internal gas pressure of 10 to 15 kg/cm² (6.5 to 7.5% swelling of the

FIG. 95. Observed Swelling of EBR-II Fuel.

Mark I fuel) we could tolerate 11 to 13% swelling in the Mark IA fuel. Assuming that the swelling characteristics of the Mark IA and the Mark I fuel are the same (the fuel pins differ only in that Mark IA is 5% shorter than Mark I and about 4 percentage points higher in enrichment) and assuming that the swelling-burnup curve can be extrapolated smoothly beyond the 1% burnup points, we would expect a burnup of about 1.4% for the Mark IA fuel elements.

It now appears that unexpected changes in the swelling characteristics of the fuel alloy accompanied the design change. The present situation can be summarized as follows:

(a) The original Mark I fuel was cast at Lemont in Building 6 in a prototype furnace similar to the production furnace later installed in the FCF at Idaho. Virgin metals were used for making the alloys. This fuel swells about 6 to 7% at 1a/o burnup of heavy atoms.

(b) About 3000 pins (designated as SL-type) of the Mark IA fuel were cast at Lemont in Building 350 in a smaller furnace of the same type fitted into a plutonium glovebox. The fuel alloy was also made from virgin metals. This fuel swells about 13 to 14% at

1 a/o burnup; approximately twice as much as the Mark I fuel.

(c) The Mark IA fuel pins (designated as MR-type) cast at Idaho in the FCF furnace, are made from melt-refined irradiated pins. This material swells about 11 to 12% at 1 a/o burnup—somewhat less than the SL-type but not much less.

(d) Some of the fuel pins (designated MRC-type) cast in FCF at Idaho, are made from melt-refining runs in which the furnace charge contains considerable amounts of reject pins and pin ends from previous castings. These are the so-called MRC melts where "C" means consolidation of scrap produced by the refabrication process. This material swells about 7 to 8% at 1 a/o burnup—about the same as the Mark I fuel cast at Lemont in the Building 6 furnace.

Swelling results for these various types of fuel material are plotted on Figure 95. The solid line at the bottom of Figure 95 represents the results of capsule irradiations in MTR which were the basis for our judgment that the U-5w/oFs alloy was quite resistant

FIG. 96. Gas Pressures as Function of Average Burnup. (1) Gas Plenum—Mark I; (2) Gas Plenum—Mark IA; (3) Gas Plenum—Mark IB; (4) Fuel Bubble—Free Swelling; (5) Fuel Bubble—Fixed Swelling ($Z = 0$); (6) Fuel Bubble—Fixed Swelling ($Z = 2.96$).

to swelling under radiation. The following comments and observations can be made:

(a) None of the EBR-II driver fuel pins behaves as well as expected from the results of the capsule irradiations in MTR.

(b) Pins from the same casting batch irradiated in the same fuel element show widely different swelling behavior.

(c) The fuel pins cast in the Lemont-350 furnace and fabricated into Mark IA fuel elements swell to a much greater degree than those cast in the Lemont-6 furnace and used in the Mark I design.

(d) The regular recycled material made in the FCF furnace swells to a greater extent in the Mark IA design than it does in the Mark I design and is only slightly better than the Lemont-350 material.

(e) Fuel pins made from melt-refining ingots, the charge that consisted largely of reject pins and pin ends from previous FCF castings, swell much less than pins made from ingots, the charge that consisted of cleaned irradiated fuel. Although not shown in Figure 95, the same effect has been noticed in the Mark I fuel.

(10) Experimental Program

We appear to be faced with a problem involving both a change in design and a change in fuel material characteristics. In an attempt to unscramble these effects the following experimental work has been started.

(a) *MR-C Type Fuel Material in the Mark IA Design*

As noted above, the MR-C type material swells about 8% at 1 *a/o* burnup. Fuel elements containing only this type of fuel should go well beyond the present 1% burnup limit before the fuel swells to the 12 to 13% range allowed by the Mark IA design. Previously, fuel elements containing well-behaved material of this type have been mixed in with elements containing rapidly swelling fuel and the maximum burnup of the fuel element is limited by the swelling characteristics of the most rapidly swelling fuel. Fuel elements are being assembled that contain only MR-C type fuel pins and will be irradiated to as high a burnup as appears safe.

(b) *Effect of Design Change*

To study the effect of design change only, it is necessary to have material of identical composition and prior history fabricated into both Mark I and Mark IA fuel elements. We have available approximately 300 fuel elements of the Mark I design from six different casting batches made in the Building 6 furnace. Presumably this material has the good swelling characteristics of the original loading. Selected

elements will be dejacketed and the fuel pins recovered. Half of the pins from each casting batch will be cut to the shorter length (the Mark IA length). The pins will then be refabricated into fuel elements, half of the Mark I and half of the Mark IA design. Fuel elements of the two designs will be loaded alternately in fuel elements and will thus experience the same irradiation regime. Any difference in swelling behavior can be attributed to the design change only.

(c) *Effect of Increased Enrichment*

The change in fuel enrichment can produce a slightly different power density and small changes in temperature profile. Two otherwise identical melts (at least they are identical within our present limit of control of the composition and cooling rates) have been prepared. One has the 48.4% enrichment characteristic of the Mark I fuel, the other is 52.5% enriched characteristic of the Mark IA fuel. Pins from both melts will be processed into Mark IA fuel elements and loaded into the same fuel element. The geometry and the irradiation regime will be identical.

(d) *Effect of Cooling Rate*

The fuel pins are injection cast into Vycor molds. The molds form a rather tight cluster of concentric hexagonal rings and are cooled by radial gas flow from the center of the cluster and by radiation to cooler outer parts of the furnace. Further, the top ends of the castings cool more rapidly than the bottom ends which are much closer to the hot crucible. In previous practice, fuel pins are identified only by melt number and the order in which they were processed. Identity with respect to position in the casting bundle and orientation (top of casting vs. bottom) was not maintained. It is believed that much of the variation in the swelling behavior of pins from a single heat can be attributed to variation in microstructure brought about by variations in cooling rates and that these variations are related to position and orientation of the pins within the mold cluster. In this experiment, fuel pins will be identified with respect to position and orientation within the casting bundle. They will be processed into Mark IA fuel elements with half of the fuel pins oriented in such a way that the top of the casting is at the top of the reactor core. The rest will be reversed end for end. The actual cooling rates at different positions within the casting bundle are difficult to measure but estimates of relative cooling rates can be made and the experiment will show whether different cooling rates affect the swelling behavior.

(e) *Effect of Trace Element Impurities*

As noted, pins cast from alloy made from rejected pins and pin ends swell less than pins made from virgin

melts or from cleaned recycled pins. The most likely explanation is that one or more beneficial impurities are being picked up during the scrap recovery operation. The most likely impurities are silicon from the Vycor molds and carbon from the casting crucible. There is also some evidence that low swelling alloy contains more aluminum than normal. Two castings will be made in the Lemont-350 facility; one will duplicate as closely as possible the SL-type material which is known to swell excessively, the second melt will use the same base stock and casting technique but will contain a few hundred parts per million each of aluminum, silicon, and carbon. Identity of pins with respect to position and orientation within the casting bundle will also be maintained (see also Item (d) above). Pins from the two melts will be loaded into the same fuel element and will thus experience the same reactor service.

(f) Hot Lab Examination of Irradiated Fuel Pins

Fuel elements of the Mark IA design and containing fuel pins cast from fuel alloy of several different sources are being examined in the Lemont hot labs. These elements have been used as driver fuel in EBR-II to burnups of up to 1 a/o. The fuel pins have been measured for dimensions and density and thus the swelling characteristics are known. The pins will be subjected to complete and detailed chemical analysis and metallographic examination by both optical and electron microscopy. Variation in composition and microstructure will then be correlated with swelling behavior and we should then know what must be done to reliably produce fuel alloy with good resistance to swelling under the existing EBR-II service conditions.

(g) Examination of Cold Unirradiated Fuel Pins

The characterization of irradiated material (Item (f) above) is somewhat slow since it must be done on highly radioactive material containing the whole gamut of fission products. We have available a few fuel pins of the original Mark I loading (pins cast in the Lemont Building 6 furnace) and of the supplemental Mark IA fuel (the SL-type material cast in the Lemont Building 350 furnace). The Lemont-6 fuel swells moderately, the Lemont-350 excessively. In general, the Lemont-350 fuel material is somewhat lower in trace-element impurities and has a larger grain size than the Lemont-6 material but the data are still scanty and incomplete.

(h) Capsuled Irradiation of EBR-II Driver Fuel

The experiments so far described pertain to the regular EBR-II driver fuel elements. This experiment involves use of the capsuled irradiation test elements

(Type A) now regularly used for experimental irradiation in EBR-II. Seven Mark IA fuel elements containing SL-type fuel pins are now under irradiation. These fuel elements will be taken to burnups well beyond (1.5 to 3.0%) the present limit of 1% for the driver fuel. Results from this experiment will be useful in evaluating the degree of conservatism in our present limitation of 1 a/o burnup maximum.

In summary, one can say that the wide variation in swelling behavior indicates that something in the material, the processing, or the design is not under control. The experiments outlined above are expected to identify the causes of these variations and would enable us to reliably prepare well-behaved material for use as EBR-II driver fuel. Clearly, if all fuel pins behaved as well as the MRC-type pins we could take the driver fuel to an appreciably higher burnup.

(11) Proposed Mark IB Fuel

Reference to Figure 94 shows that the swelling and hence the burnup of the Mark IA fuel is still pneumatically limited, that is, limiting internal gas pressure is reached before the fuel has swelled to the jacket [marked—Mechanical Restraint ($Z = 0$)] or to the jacket and the restrainer [marked—Mechanical Restraint ($Z = 2.96\%$)]. Further relaxation of the pneumatic restraint is obtained by removing volume from the restrainer and by decreasing the overlay of sodium. The resulting pressure vs. swelling curve is labeled Mark IB on Figure 94. It should be noted that in this case the fuel can swell to the jacket (mechanical restraint, $Z = 0$) or to the jacket and to the restrainer (mechanical restraint, $Z = 2.96\%$) before the pressure in the gas plenum becomes intolerably high. The Mark IB fuel element differs from the Mark IA in the following respects:

(a) The restrainer is simpler and less massive. It consists of a top plug which becomes part of the final weld closure of the fuel element and a central wire of small diameter (No. 18 B & S) which will have a cross wire welded to the lower end to center the lower tip in the jacket. Most of the volume which is removed from the restrainer is added to the gas plenum volume.

(b) The sodium overlay above the fuel pin is decreased. The holdup of sodium above the bottom of the restrainer is now negligible and extra overlay sodium is not required to ensure submergence of the fuel pin in liquid sodium. The fuel element thus contains less sodium with its high thermal expansion coefficient and the volume of the excess sodium no longer needed can now be added to the gas-plenum volume.

The pertinent design data are given in Tables 44 and 45. The calculated gas plenum pressures are given by

$$P_g = \frac{64.527}{23.147 - Y} \quad (\text{Mark IB})$$

and are tabulated in Table 46 and plotted in Figure 97. A new situation arises that is not encountered in the Mark I and Mark IA design: fuel swelling stops abruptly at about 17 % (point 1) or at 20 % (point 2) depending upon which of the mechanical restraints operate, and the gas plenum pressure also reaches a plateau. In this case, the burnup problem requires a somewhat different analytic approach.

We will consider that the total swelling of the fuel is made up of two parts: one due to the accumulation of solid (nonvolatile) fission products, the second due to the formation of gas bubbles of inert gas (Xe and Kr). Assuming that the bubbles are all of the same size, we can write:

$$P_b = 1.0197^{-10} (N_0 \cdot k) (\Sigma A_{fp}) (\rho) \cdot (T_f) \left(\frac{w/o \text{ U}}{\text{Au}} \right) \cdot \left(\frac{\text{Bu}}{Y - R \cdot \text{Bu}} \right) \quad (6)$$

where

P_b = pressure of fission product gas in the bubbles in kg/cm^2

N_0 = Avogadro Number = 6.02322×10^{23}

k = Boltzmann Constant = 1.3804×10^{-16}

ΣA_{fp} = number of gaseous fission product (Xe + Kr) atoms formed per 100 fissions = 24.9 (see ANL-5743)

$w/o \text{ U}$ = weight percent uranium (all isotopes) in fuel alloy

Au = atomic weight of uranium, adjusted for isotopic composition

ρ = density of fuel alloy in gm/cm^3

T_f = volume averaged operating temperature of the fuel

Bu = atomic percent burnup of heavy atoms

R = percent increase in volume of fuel per 1a/o burnup from nonvolatile fission products

Y = percent volume increase (total) of fuel after Bu % burnup

Putting in the constants we have:

$$P_b (\text{kg/cm}^2) = 0.02450 \cdot \rho \cdot T_f \left(\frac{w/o \text{ U}}{\text{Au}} \right) \left(\frac{\text{Bu}}{Y - R \cdot \text{Bu}} \right) \quad (6a)$$

This relationship is a somewhat mixed bag in that it involves the composition, the enrichment (through the Au term), the density, the operating temperature and the free swelling characteristics of the fuel. For the U-5w/oFs alloy of 52.5 % enrichment:

$$w/o \text{ U} = 95$$

$$\text{Au} = 236.48$$

$$T_f = 825^\circ\text{K} \text{ (45 Mw operation)}$$

$$\rho = 18.12 \text{ g/cm}^3$$

and hence,

$$P_b = 1267.3 \left(\frac{\text{Bu}}{Y - R \cdot \text{Bu}} \right) \quad (6b)$$

To complete the calculation we need a value for R and the total swelling (Y) as a function of burnup (Bu). R is not too well established, it appears to lie between 2 and 3; we will use $R = 2.5$. Figure 95 shows that the swelling is a highly variable function of the burnup. We will assume that, with better control of fuel preparation, we will be able to produce material having the swelling characteristics of the Mark I or of the Mark IA MRC-type melts and that we can relate swelling to burnup through the relationship:

$$Y = 6.80 \cdot \text{Bu}^2 \quad (5)$$

Making these substitutions, we have finally

$$P_b = \frac{186.4}{\text{Bu} - 0.368} \quad (\text{for free swelling}) \quad (6c)$$

Fig. 97. Calculated Jacket Hoop Stresses. (1) Mark I + 100°C; (2) Mark I; (3) Mark IA; (4) Mark IB ($Z = 0\%$, $Y = 16.84\%$); (5) Mark IB ($Z = 2.96\%$, $Y = 20.30\%$).

In all cases, we assume $Y = 6.80 \text{ Bu}^2$.

TABLE 47. CALCULATED FUEL BUBBLE PRESSURES

a/o Burnup (Bu)	$P_b =$	$P_1^* =$	$P_2^* =$
	$\frac{186.4}{\text{Bu} - 0.368}$	$\frac{506.9 \cdot \text{Bu}}{6.736 - \text{Bu}}$	$\frac{506.9 \cdot \text{Bu}}{8.120 - \text{Bu}}$
0	—	—	—
0.2	—	—	—
0.4	5825	32	26
0.6	803	50	40
0.8	431	68	55
1.0	295	88	71
1.2	224	110	88
1.4	181	133	106
1.57	155	155	122
1.6	151	158	124
1.73	137	175	137
1.8	(130)	185	144
2.0	(114)	214	166
2.2	(102)	246	188
2.4	(92)	281	213

The equation has the rather interesting property that the pressure in the gas bubbles decreases as the burnup and the amount of gas increases. The calculated values are tabulated in Table 47 and plotted as curve 4 on Figure 96.

However, free swelling does not proceed indefinitely. At the points marked 1 or 2 on Figure 94, the mechanical restraints prevent further increases in fuel volume, Y becomes constant and our equations for gas bubble pressure become:

$$P_1^* = \frac{506.9 \cdot \text{Bu}}{6.736 - \text{Bu}} \quad \text{if} \quad \begin{array}{l} Z = 0\% \text{ (point 1)} \\ Y_1 = 16.84 \end{array} \quad (6d)$$

or

$$P_2^* = \frac{506.9 \cdot \text{Bu}}{8.120 - \text{Bu}} \quad \text{if} \quad \begin{array}{l} Z = 2.96\% \text{ (point 2)} \\ Y_2 = 20.30 \end{array} \quad (6e)$$

These calculated bubble pressures are tabulated in Table 47 and plotted as curves 5 and 6 on Figure 96. The pressure now increases with increasing burnup.

At this point it becomes desirable to recast the analysis in terms of jacket stress rather than internal gas pressure. While the fuel is swelling freely, it is not in contact with the jacket, the high internal pressures in the gas bubbles are contained by surface tension, by the mechanical strength of the fuel, and the rather nominal gas plenum pressure. The only pressure the jacket must restrain is that in the gas plenum (Table 46). We can then write for the free swelling case:

$$P_b = P_s + P_m + P_g \quad (7)$$

where

P_b = the calculated gas bubble pressure within the

fuel, assuming the swelling function $Y = 6.80 \text{ Bu}^2$

P_s = the pressure restrained internally by the surface tension of the fuel material

P_m = the pressure restrained internally by the mechanical strength of the fuel material

P_g = the restraint exerted by the external pressure in the gas plenum

Reference to Figure 97 shows that over most of the irradiation period, the external restraint (P_g) is nearly constant. The relatively rapid decrease in bubble pressure (P_b) with increasing burnup means that the internal restraints (P_s and P_m) decrease with increasing burnup. We can use the free swelling curve to evaluate the internal restraints ($P_s + P_m$).

Beyond the points (1') or (2') of Figure 96, free swelling is prevented by the mechanical restraints and the gas-bubble pressure rises along the curves 5 or 6. The internal restraints are insufficient to contain the increased pressure and additional external restraint is required to prevent fuel swelling. We will assume that there exists an external pressure (P_g^*) that is just sufficient to prevent the fuel from contacting the jacket and restrainer, that is, which is sufficient to prevent fuel swelling beyond the limits set by the mechanical restraints. We can then write:

$$P_b^* = P_s + P_m + P_g^* \quad (7a)$$

P_g^* is now the pressure which must be contained by the jacket.

We can define the term "excess pressure" (P_{ex}) as the difference between the fuel bubble pressure during free swelling and under the condition of fixed swelling, that is,

$$\begin{aligned} P_{ex} &= P_b^* - P_b = (P_s + P_m + P_g^*) - (P_s + P_m) + P_g \\ &= P_g^* - P_g \end{aligned}$$

or

$$P_g^* = P_{ex} + P_g \quad (8)$$

This fictitious gas pressure (P_g^*) can then be converted into a jacket loop stress through the usual relationship:

$$\sigma_j^* = \left(\frac{K^2 + 1}{K^2 - 1} \right) (P_g^*) \quad (9)$$

We will consider two cases for the evaluation of P_{ex} . In case I, we will assume that, when the mechanical restraints operate and the fuel body is no longer increasing in volume, the internal restraints become constant at the values corresponding to the pressures at points (1') or (2'). In case II, we assume that the internal restraints continue to decrease along the pro-

section of the free swelling curve (curve 4) of Figure 96. These two cases are marked on Figure 96 for fuel swelling to the jacket and to the restrainer.

It should be noted that at burnups below the mechanical restraint cut-offs, the excess pressure is zero (free swelling condition) and the pressure which the jacket must contain is simply the gas plenum pressure (P_g). Above the mechanical cut-off points the jacket must withstand an additional pressure (P_{ex}) which depends upon the burnup and also upon what we assume the internal restraints to be.

The calculated jacket hoop stresses as a function of average fuel burnups are plotted in Figure 97. Curves 4 and 5 assume that the internal restraints become constant at the mechanical cut-off points [that is, we use $(P_{ex})_1$, of Figure 96]. For reference purposes, we have also plotted the calculated hoop stresses for the Mark I and Mark IA fuel elements. In all cases we assume that the swelling-burnup relationship can be expressed by:

$$Y = 6.80 \text{ Bu}^2 \quad (5)$$

and that this relationship can be extrapolated beyond

the 1% burnup value which is as far as our direct experimental observation goes (see Figure 95).

If we accept the Miller Criterion for allowable hoop stress [$\sigma_j = (YS) - (\sigma_{th}/4)$], then for Type 304 stainless steel, we can calculate $\sigma_j \simeq 900 \text{ kg/cm}^2$. This value is also marked on Figure 97. This criterion is not applicable to Mark I or Mark IA fuel elements because of the very rapid change in hoop stress with burnup (curves 1, 2, and 3). In the case of Mark IB, the rate of change is much less (curves 4 and 5) and it might be possible to work much closer to the limit set by the properties of the jacket.

One final comment is in order regarding curves 4 and 5 of Figure 97. We know that the burnup and the swelling of the fuel pin are not uniform from end to end but are a maximum over the central portion. We can apply the same analysis used in deriving curves 4 and 5 to the central portion of the fuel pin, using maximum burnup rather than average burnup and a swelling equation based on maximum burnup. To a fair approximation, curves 4 and 5 represent the jacket stress at the midlength of the fuel element if we read the burnup as maximum rather than average.

C. NUCLEAR SAFETY

1. Radiation Measurements and Personnel Exposures Encountered during Fabrication of Reactivity-Coefficient Specimens (T. A. STEELE*)

In continuation of the investigation initiated last year,⁽⁴¹⁾ radiation measurements, dose-rate computations and the study of personnel radiation exposures during the fabrication of high-burnup plutonium** have been made.

Radiation measurements from available plutonium have assisted in establishing current fabrication procedures that minimize radiation exposures of personnel—both whole body and extremity. These measurements have also assisted in refining a computer program to yield more reliable dose-rate computations associated with high-burnup plutonium. Radiation exposures incurred during the fabrication of Pu-1.1w/oAl (with the isotopic composition of the plutonium consisting of 72w/o²³⁹Pu, 22.1w/o²⁴⁰Pu, 4.6w/o²⁴¹Pu and 0.67 w/o²⁴²Pu) into reactivity-coefficient fuel elements have been determined for the separate fabrication operations. The information derived from these investigations has assisted in establishing radiation-protection requirements for fabricating the future recycled plutonium reactor fuel.

Radiation Measurements and Calculations

Surface exposure-rate measurements have been made with an extrapolation chamber. This chamber has yielded the results listed in Table 48.

These measurements have been used to check the computer calculated values shown in Figure 98 for the isotopic compositions listed in Table 49.

The computed and measured values agree to $\pm 25\%$ for times of one year after separation.

Radiation Exposures

The radiation exposures associated with the fabrication of reactivity coefficient fuel elements have been monitored with the ANL film badge. The exposure data accumulated for separate fabrication operations are shown in Table 50. These exposures are reported per kilogram of plutonium and are based on the fabrication of approximately 13 kilograms of the 22w/oPu²⁴⁰ material into fuel elements passing all final inspections. The

* T. A. Steele, Industrial Hygiene and Safety Division, Building 350.

⁽⁴¹⁾ Shuck, A. B., et al, *Radiation Dose Rate from High-Burnup Plutonium*, ANL-7155, pp. 53-55.

** Material with less than 80% ²³⁹Pu is considered as high-burnup plutonium.

exposures associated with each of these operations includes the normal weighing and transferring of the material. These values can be considered accurate to $\pm 30\%$.

The largest exposure occurs during the secondary working operation as the source then has a large surface area and is difficult to shield. The lowest exposure occurs during the loading and welding operations. In these operations, local shielding around the source reduces the exposure while not hindering the operation.

From the information derived in this investigation it can be seen that the radiation exposure is a function of the weight, geometry and age of the plutonium, fabrication operation, shielding utilization, and the amount of material fabricated. Some of these factors can be modified to enable more production with lower radiation exposure. The following guidelines have been established to achieve these goals.

1. Early fabrication after chemical separation;
2. Shielding applied to equipment within the gloveboxes and the glovebox surfaces;
3. Use of leaded glass for selected glovebox windows;
4. Immediate removal of plutonium residues from the glovebox system;
5. Use of light-leaded gloves and mechanical techniques for handling the plutonium;
6. Monitoring of extremity and whole body exposures to enable rotation of personnel for tasks having high exposure rates;
7. Preplanning fabrication procedures to reduce exposure times to a minimum;

TABLE 48. EXTRAPOLATION CHAMBER MEASUREMENTS

Source Isotopic Weight Percent					Source Weight, grams	Time After Purification (Approx.)	Surface Exposure Rate, r/hr
²³⁸ Pu	²³⁹ Pu	²⁴⁰ Pu	²⁴¹ Pu	²⁴² Pu			
0.02	80.91	16.67	2.15	0.27	30.2	8 months	2.92 $\pm$ 0.17
						9 months	3.34 $\pm$ 0.2
						11 months	3.7 $\pm$ 0.22
						1 year	3.81 $\pm$ 0.23
0.034	72.55	22.16	4.62	0.67	21.6	10 months	4.5 $\pm$ 0.27
						11 months	5.0 $\pm$ 0.3
0.034	72.55	22.16	4.62	0.67	40.9	8 months	4.1 $\pm$ 0.2
						9 months	4.55 $\pm$ 0.2
						10 months	4.95 $\pm$ 0.3
						11 months	5.44 $\pm$ 0.33

350-887

FIG. 98. Calculated X- and Gamma-ray Surface Dose Rate from a Slab for Various Plutonium Isotopic Compositions.

8. Use of shielded temporary storage areas in the glovebox system; and

2. Penetration of Jacket Materials by Molten U-Pu-Zr and U-Pu-Ti Alloys (H. ŠAVAGE)

The U-Pu-Zr and U-Pu-Ti alloys developed for higher-temperature reactor application were tested for their rate of molten penetration into selected jacket materials. The rate of penetration and the factors influencing it are directly related to studies of fuel-element failures that occur near or slightly above the normal operating temperature. Similar studies have been conducted on uranium and uranium-5w/o fissium against Type 304 stainless steel and unalloyed iron.^(42,43)

⁽⁴²⁾ Walter, C. M., and Kelman, L. R., *Penetration Rate Studies of Stainless Steel by Molten Uranium and Uranium-Fissium Alloy*, J. Nucl. Matls. 6(3), 281-290 (1962).

TABLE 49. PLUTONIUM ISOTOPIC COMPOSITIONS STUDIED^(a)

Source	²³⁸ Pu	²³⁹ Pu	²⁴⁰ Pu	²⁴¹ Pu	²⁴² Pu
A	0.00001	95.01	4.51	0.47	0.01
B	0.0001	91.15	8.00	0.80	0.05
C	0.002	80.91	16.69	2.15	0.267
D	0.020	76.68	20.00	3.00	0.3
E	0.030	72.55	22.16	4.60	0.666
F	1.000	64.00	20.00	12.00	3.00
G	0.040	62.76	30.00	6.00	1.20
H	2.000	40.00	30.00	18.00	10.00
I	0.100	34.90	35.00	10.00	20.00
J	0.200	4.80	25.00	10.00	60.00
K	0.300	0.70	2.00	1.00	96.00

^(a) All in weight percent.

TABLE 50. RADIATION EXPOSURE PER FABRICATED KILOGRAM OF MATERIAL^(a)

Fabrication Operation	Whole-Body Exposure, rem/kg	Extremity Exposure, rem/kg
Alloying and casting ingot	0.075	0.2
Secondary working (rolling-blanking)	0.215	0.35
Cleaning	0.1	0.13
Loading	0.04	0.05
Welding and inspection	0.045	0.06

^(a) Pu-1.1Al with 22w/o²⁴⁰Pu, 72w/o²³⁹Pu, 4.6w/o²⁴¹Pu, and 0.67w/o²⁴²Pu constituting the Pu.

9. Knowledge of plutonium isotopic compositions, light element analysis, and time after plutonium separation.

Molten penetration by melts of U-15w/oPu-10w/oZr and U-15w/oPu-6.5w/oTi alloy into tubes of Type 304 stainless steel and V-20w/oTi alloy was studied from about 1200°C to 1450°C. The penetration rate increases with increasing temperature, and it is about ten times higher with Type 304 stainless steel. A plot of the penetration rate versus temperature is shown in Figure 99 for U-15w/oPu-10w/oZr against Type 304 stainless steel. There is wide scatter in the results and no regular change in the penetration rate with wall thickness. A similar plot for U-15w/oPu-6.5w/oTi against V-20

⁽⁴³⁾ Walter, C. M., and Kelman, L. R., *The Interaction of Iron with Molten Uranium*, J. Nucl. Matls. 20(3), 314 (1966).

47960

FIG. 99. Penetration Rate vs Temperature for Different Wall-thickness Specimens of Type 304 SS in Molten U-15w/oPu-10w/oZr Alloy.

47959

FIG. 101. Penetration Rate vs Temperature for Specimens of V-20w/oTi in U-15w/oPu-10w/oZr Alloy.

47957

FIG. 100. Penetration Rate of V-20Ti Tubes by Molten U-15w/oPu-6.5w/oTi Alloys.

47954

FIG. 102. Schematic of the Type 304 Stainless Steel Specimen Penetrated by U-15w/oPu-10w/oZr. The numbers correspond to the numbered areas in Table 51.

TABLE 51. COMPOSITIONS OF PHASES DETERMINED BY MICROPROBE INTENSITY RATIOS IN A COUPLE: TYPE 304 STAINLESS STEEL AGAINST MOLTEN U-15w/oPu-10w/oZr ALLOY

Area ^(a)	Compositions of Phases (w/o)									
Electron Current Image.....	1	2	3	4	5	6	7	8	9	10
Element	Grey continuous	Dark sub grains	Light bdy. ^(b)	Dark sub grains	Light bdy. ^(b)	Dark sub grains	Light areas	Light areas	Grey areas	Dark areas
Ni	8.6	4.7	12.4	2.7	1.1	4.0	7.3	2.5	4.1	3.0
U	0	0	23.3 30.3 ^(c)	0.3	31.7	10.3	22.9	60.4	42.9	25.4
Fe	62.3	62.3	38.9	65.1	37.9	55.6	26.5	10.0	27.2	31.0
Pu	0	0.1	5.0 6.5 ^(c)	0.1	5.2	1.4	12.2	15.0	5.1	3.6
Cr	23.9	28.8	6.4	32.6	3.6	28.3	7.1	0.2	8.9	10.4
Zr	0	0	2.9	0	5.6	1.3	7.8	0.1	3.7	13.0
Total Percentage	94.8	95.8	88.9 ^(d)	100.8	85.1	100.9	83.8	88.2	91.9	86.4

(a) Area 1: unaffected SS matrix; Areas 2 and 3, solid state penetrated region; Areas 4, 5, 6, 7, 8, 9, and 10, molten region.

(b) Bdy—boundary.

(c) Corrected for absorption and atomic number.

(d) Corrected total is 101.3%.

TABLE 52. COMPOSITIONS OF PHASES DETERMINED BY MICROPROBE INTENSITY RATIOS IN A COUPLE: V-20w/oTi AGAINST MOLTEN U-15w/oPu-6.5w/oTi ALLOY

Area.....	Composition of Phases (w/o)							
Electron Current Image....	1	2	3	4	5	6	7	8
Element	Very dark	Dark	Light	Dark	Light	Dark	Grey	Light
Ti	21.6	22.0	11.5	22.4	3.9	20.5	16.3	5.3
V	79.3	46.1	6.2	39.0	3.5	39.0	21.9	3.2
U	0	21.5	69.9	28.0	73.3	25.2	54.3	74.0
Pu	0	1.7	8.8	2.2	19.1	2.9	5.5	14.5
Total Percentages	100.9	91.3	96.4	91.6	98.8	87.6	98.0	97.0

w/oTi is shown in Figure 100. Again there is wide scatter in the data, and no dependence on wall thickness of the penetration rate. Data were limited to temperatures above 1290°C because of the high melting point of this alloy. The penetration of V-20w/oTi by U-15w/oPu-10w/oZr is shown in Figure 101. At 1350 and 1400°C, the penetration rate into V-20Ti is about the same for either fuel alloy. However, the U-Pu-Zr fuel alloy penetrates faster at 1300°C.

The wide scatter in the experimental data is partly caused by cladding defects and variations in the molten fuel. The method depends on a penetration of the tube wall and electrical contact of an enclosed wire with the melt. The wall may be weaker in one area than another, and may fail sooner than would be predicted on the basis of the average penetration rate. There may be impurities in the melt adjacent to the wall, effectively separating it from the liquid. Liquid circulation persists

in the melt, and further complicates the final penetration rate by an amount that has not been measured.

Both visual and electron-microprobe studies of specimens penetrated at 1350°C of both Type 304 stainless steel by U-15w/oPu-10w/oZr and V-20w/oTi by U-15w/oPu-6.5w/oTi were made. These studies are summarized in Tables 51 and 52, and Figures 102 and 103. The numbered areas at the top of the tables correspond to the numbers on the illustrations. The penetration mechanism, indicated by these slowly cooled, failed specimens, is apparently a dissolution process where the liquid penetrates the solid and particles of solid are removed by solution and convection. The attack occurs preferentially around subgrains in the solid. A viscous layer is built up through which the molten uranium passes to the solid, and the particles of solid and dissolved solid pass to the melt. There is some solid-state penetration indicated because the specimens are not

FIG. 103. Schematic of the V-20Ti Specimen Penetrated by U-15 Pu-6.5Ti(w/o) Alloy at 1350°C.

47953

FIG. 104. Rate of Penetration of Type 304 Stainless Steel by U-15w/oPu and U Containing Various Amounts of Carbon.

quenched after withdrawal from the melt. The melt interface is outlined in some cases by porosity or slag inclusions.

The characteristics of the melt are affected by the graphite crucible used. A series of tests with a relatively pure uranium-15w/o plutonium melt contained in a zirconia crucible was made over the temperature range 1100 to 1400 $^\circ C$. The results are shown in Figure 104. The rate generally increases from about 0.02 mm/sec at 1180 $^\circ C$ to about 10 mm/sec at 1400 $^\circ C$. The rate increases reasonably well with temperature, and tubes with different wall thicknesses are penetrated at the same rate. Additional runs were made in which uranium with various amounts of carbon was used for tests in a similar zirconia crucible. Most of the data in Figure 104 indicate that carbon decreases the penetration rate.

Two molten penetration mechanisms have been described.⁽⁴⁴⁾ One is based on the boundary layer model where the dissolution rate is controlled by diffusion through this viscous layer; the other is based on a surface chemical reaction that proceeds at the limiting rate. At activation energy of 140 kcal/g atom was calculated for the penetration of Type 304 stainless steel by U-15w/oPu alloy. This information is not sufficient alone to establish the mechanism.

⁽⁴⁴⁾ Kassner, T. F., *A Convective-Diffusion Study of the Dissolution Kinetics of 304 Stainless Steel in the Bismuth-Tin Eutectic Alloy*, ANL-6985 (November 1965).

D. DEVELOPMENT OF CERAMIC FUELS

1. Thermal Stability of Plutonium Ceramics

a. Gd_2O_3 EVAPORATION EXPERIMENTS (D. R. MESSIER)

An evaporation study was made on gadolinium sesquioxide to test the thermogravimetric apparatus, and to obtain data that would augment published data.⁽⁴⁵⁾

Two techniques were employed for the evaporation experiments⁽⁴⁶⁾: the Langmuir technique, which measures the rate of evaporation from an exposed surface, and the Knudsen cell technique, which measures the rate of effusion of vapor from a small orifice in a cell containing material assumed to be in equilibrium with its vapor. Specimens were either placed in an open tungsten crucible or suspended on a rhenium wire for Langmuir-type measurements. Two cells having different orifice diameters were used for the Knudsen runs.

Plots of weight-loss versus time for a Gd_2O_3 pellet evaporating from a tungsten crucible are shown in Figure 105. Similar linear evaporation rates were observed in all of the evaporation runs. The linearity of the plots indicates that evaporation is congruent, i.e., the compositions of the vapor and solid are identical. Experiments, wherein specimens were evaporated completely from the crucible and a cell, showed that reaction with tungsten had a negligible effect on the weight-loss results.

Thermodynamic calculations were made on the assumption that the evaporation reaction is^(45,47)

Partial pressures of GdO and atomic oxygen were calculated by use of an expression of the general form⁽⁴²⁾

$$P(\text{atmos}) = \frac{2.26 \times 10^{-2}}{W} m_i (T/M_i)^{1/2}$$

where m_i and M_i are respectively the evaporation rate ($\text{g cm}^{-2} \text{sec}^{-1}$), and the molecular weight (g mole^{-1}) for a given vapor species. Clausing correction factors, W , were applied to the crucible and cell data to correct for the resistance of a channel to molecular flow.

A plot of log oxygen-pressure versus reciprocal tem-

perature for all of the experimental data is shown in Figure 106. Equations that fit the data are

$$\log_{10} P_0 = 8.316 \pm 0.363 - \frac{(35.342 \pm 0.814) \times 10^3}{T} \quad (\text{Langmuir})$$

$$\log_{10} P_0 = 6.813 \pm 0.486 - \frac{(31.774 \pm 1.219) \times 10^3}{T} \quad (\text{Cell No. 1})$$

$$\log_{10} P_0 = 6.830 \pm 0.160 - \frac{(31.977 \pm 0.396) \times 10^3}{T} \quad (\text{Cell No. 2})$$

where P_0 is the oxygen-pressure (atmos), and T is the absolute temperature ($^\circ\text{K}$).

The reason for the difference in the slopes of the Knudsen and Langmuir data plots shown in Figure 106 is unknown. If, however, a single line were drawn through all of the data points, its slope would not be much different than the slopes shown for the data of the Knudsen cells. Whether a real break or curvature exists in the plot of log oxygen-pressure versus $1/T$ is therefore questionable.

Heats of vaporization calculated from the Knudsen cell data by second and third law methods were in excellent agreement, lending confidence in the measurement procedure. Through use of the cell data, an average value of $\Delta H_0^\circ = 464.0 \pm 1.0$ kcal per mole was obtained for the assumed evaporation reaction.

b. PuO_2 AND $(\text{U,Pu})\text{O}_2$ EXPERIMENTS (D. R. MESSIER)

Preliminary work was begun on the evaporation behavior of PuO_2 and $(\text{U,Pu})\text{O}_2$ compositions. This work involved preparation and characterization of specimens, and Langmuir-type evaporation experiments on PuO_2 .

Experiments were made to determine oxygen-to-metal (O/M) ratios on pelletized specimens of PuO_2 and $80w/o\text{UO}_2\text{-}20w/o\text{PuO}_2$. O/M ratios in PuO_2 pellets were determined by oxidizing them to PuO_2 through heat treatment for one hour at 1470°K in a flowing atmosphere of helium-1 *v/o* oxygen.⁽⁴⁸⁾ At

⁽⁴⁵⁾ White, D. E., Walsh, P. N., Ames, L. L., and Goldstein, H. W., "Thermodynamics of Vaporization of the Rare-Earth Oxides at Elevated Temperatures," *Thermodynamics of Nuclear Materials*, p. 417-443 (IAEA, Vienna, 1962).

⁽⁴⁶⁾ Dushman, S., *Scientific Foundations of Vacuum Technique*, 2nd Ed. (John Wiley and Sons, Inc., New York, 1962).

⁽⁴⁷⁾ Panish, M. B., *Vaporization of the Rare Earth Oxides*, J. Chem. Phys., **34**, 2197-8 (1961).

⁽⁴⁸⁾ Marken, T. L., Walter, A. J., and Bones, R. J., *The Determination of Oxygen/Metal Ratios for Uranium, Plutonium and (U·Pu) Oxides*, AERE-R 4608 (1964).

tempts that were made to analyze mixed-oxide specimens by the method described by Lyon⁽⁴⁹⁾ were unsuccessful. Specimens repeatedly fractured upon oxi-

43790

FIG. 105. Typical Plots of Weight Loss vs Time for the Evaporation of a Gd_2O_3 Pellet in a Tungsten Crucible.

45533

FIG. 106. Pressure of $O(g)$ Over $Gd_2O_3(s)$ Calculated from the Knudsen-Cell Data.

TABLE 53. REACTIONS OF PuO_2 WITH CONTAINER MATERIALS

Temperature, °C	Furnace Atmosphere	Container	Remarks
1000	Helium-0.375 v/o oxygen	Alumina boat.	Powder sample discolored, boat cracked.
1505	Vacuum	Tungsten plate in tungsten crucible.	Extensive reaction, pellet stuck firmly to tungsten plate.
1610	Vacuum	Molybdenum plate in tungsten crucible.	Moderate reaction, plate and crucible lost weight, pellet did not stick.
1200	Helium-1.0 v/o oxygen	Platinum boat.	No reaction of pellet with platinum.
1490	Vacuum	Iridium plate in tungsten crucible.	No apparent reaction between iridium and pellet, some reaction between iridium and tungsten.
1502	Vacuum	Molybdenum crucible.	Moderate reaction, crucible lost weight.
1738	Vacuum	Rhenium wire coil.	Slight reaction, coil lost weight.

dation at 970°K. It therefore appears that additional work is needed to develop a nondestructive analysis technique.

Unexpected difficulties were encountered in finding a suitable, nonreactive container for PuO_2 evaporation experiments. Table 53 summarizes the results of high temperature tests of the compatibility of PuO_2 with

various refractories in several atmospheres. Iridium appears to be the least reactive of the container materials at temperatures no less than 1400°C, and further tests will be made when iridium crucibles are obtained.

Preliminary evaporation experiments were made on PuO_2 pellets contained in a rhenium wire coil. After initial periods of decreasing rate, rates of weight loss became almost constant for specimens run *in vacuo* at 1976°K and 2011°K. The final O/M was about 1.92 for both specimens. Additional evaporation runs are now in progress.

⁽⁴⁹⁾ Lyon, W. L., *The Measurement of Oxygen to Metal Ratio in Solid Solutions of Uranium and Plutonium Dioxides*, GEAP-4271 (1963).

2. Uranium-Mixed Anion Systems

a. THE U-S-O SYSTEM (P. D. SHALEK)

Condensed-phase relations in the system U-S-O are being investigated in order to better understand the effects of oxygen contamination on the properties of uranium monosulfide, a potential fuel material. Figure 107 shows an isothermal section of the system at 1200°C. The area under investigation is bounded at the corners by uranium, UO_2 and US_2 . The uranium is obtained as a fine powder from the hydriding-dehydriding cycle, the US_2 is prepared by reacting the uranium powder with H_2S to saturation, while the UO_2 is obtained commercially. These powders are mechanically blended, isostatically pressed into pellets at 3860 kg/cm² without binder, and sintered in vacuum with each pellet being individually enclosed in a loosely covered tungsten crucible to more nearly approximate equilibrium vapor conditions. Melting temperatures are determined by using a modified Mendenhall wedge in helium.

Initially it was of interest to become familiar with the characteristic properties of the compounds found in the system. They were all prepared, at near stoichio-

metric composition (as ≥ 99 w/o single-phase material excepting U_3S_5 which contained 4 to 5 w/o U_2S_3), and their melting points were determined and are shown in Figure 107. The high-temperature α - US_2 polymorph was observed to decompose, variously, to the α -structure with a reduced S/U ratio of 1.88 at 1280°C, to U_3S_5 slowly at 1450°C, and to U_2S_3 during the rapid (1 to 2 minutes) melting-point determination. The thermal stability of the compounds, as represented by melting point, was roughly proportional to the theoretical density as shown in Table 54. Also given in the table are the lattice parameters determined from Debye-Scherrer patterns and the measured value of room temperature electrical resistivity. These latter measurements show that solid types in the system run all the way from metals to an insulator. The U_3S_5 phase appeared to have an especially high thermoelectric power.

Oxidation characteristics of US and US_2 were found to be basically similar in flowing oxygen in a DTA apparatus. The first characteristic reaction was a strong exotherm in which the sulfide was oxidized to $\text{UO}_2(\text{S})$ (the (S) here indicating sulfur retained in the UO_2

FIG. 107. Isothermal Section of the System U-S-O at 1200°C.

TABLE 54. SOME PROPERTIES OF COMPOUNDS IN THE SYSTEM U-S-O

Compound	Lattice (Structure); Parameters in Å	Theoretical Density (g/cc)	Melting Point (°C)	Resistivity (Ω-cm)
US	Cubic (NaCl); $a_0 = 5.486$	10.83	2440	2.63×10^{-4}
U ₂ S ₃	Orthorhombic (Sb ₂ S ₃); $a_0 = 10.35$, $b_0 = 10.61$, $c_0 = 3.87$	8.81	1775	7.75×10^{-4}
U ₃ S ₅	Orthorhombic; $a_0 = 7.44$, $b_0 = 8.11$, $c_0 = 11.78$	8.26	1695	4.30×10^{-2}
αUS ₂ (S/U = 1.88)	Tetragonal (PbCl ₂); $a_0 = 10.30$, $c_0 = 6.32$	7.42	Dissoc. at 1400	1.71×10^{-3}
UOS	Tetragonal (PbFCl); $a_0 = 3.844$, $c_0 = 6.694$	9.70	1925	$(0.2-7.9 \times 10^{-2})^{(50)}$
UO ₂	Cubic (CaF ₂); $a_0 = 5.471$	10.97	2750	$(1.41 \times 10^2)^{(12)}$

structure), the second was a much weaker exotherm at 540°C in which UO₂(S) oxidized to U₃O₈(S), and the third was a weak endotherm at 770°C where the U₃O₈(S) decomposed to U₃O₈ + S↑. In a prolonged oxidation cycle it was found that up to half the original S content of US was retained up to the decomposition temperature. Oxidation resistance increased with the temperature stability of the disulfide polymorph, the strong exotherm occurring at 300°C for γUS₂, at 315°C for βUS₂ and at 375°C for αUS₂ as compared with 400°C for US. UOS oxidized directly to U₃O₈(S) at about 540°C with retained sulfur again being liberated at 770°C.

Multiphase equilibria were observed in two portions of the system. Compositions on the UO₂-US₂ join ranging from UO_{1.05}S_{0.95} to UO_{0.93}S_{1.08} (as mixed) and others on the U₃O₈-US₂ join were first examined at 1200°C. The latter group lost sulfur and proceeded into the UOS-UO₂ two-phase area. At 1200°C the UOS phase was ≤ stoichiometric in uranium and sulfur and showed only a small range for hyperstoichiometric oxygen. At 1650°C, however, the UOS solid solution area had expanded to include at least an equivalent 40UO₂-60UOS composition. Systematic *d*-spacing changes indicated that, with increasing oxygen content, the tetragonal UOS unit cell was contracting in the *c*-direction while remaining constant in the *a*-direction. This would be expected, to a point, if oxygen were replacing sulfur atoms in the sulfur layers which lie perpendicular to the *c*-axis of this completely layered structure.

Samples having nominal compositions in the range from US_{0.85} to US_{2.0} on the U-S baseline were sintered at 1450°C. Since there was known to be 0.2 to 0.4 *w/o* oxygen in these materials and no secondary oxide phases were observed metallographically, there must be significant solubility for oxygen in all the sulfide compounds. Limited lattice parameter variation indi-

TABLE 55. CHEMICAL ANALYSIS OF UAS

Sample No.	Found				Theoretical	
	% U	% As	% O	As/U Ratio ^a	% U	% As
4	75.92	23.89	0.19	1.02	76.07	23.93
5	75.80	23.99	0.21	1.03	—	—

^(a) Uranium in the secondary UO₂ phase was excluded from calculation of the As/U ratio.

cated that the homogeneity range for sulfur in US is only slight at this temperature. The area within 10 *a/o* of US is being intensively investigated using electrical resistivity and microhardness measurements in conjunction with routine X-ray, metallographic and chemical analyses in order to identify systematic property trends both in the solid solution and multiphase areas.

b. SYNTHESIS AND PROPERTIES OF URANIUM MONOARSENIDE (Y. BASKIN)

Uranium monoarsenide was synthesized by first reacting finely divided uranium with arsine (H₃As) gas. The uranium was rendered very fine by passing it through several hydriding and dehydriding cycles. Reaction with H₃As was carried out at 300°C to mitigate dissociation of the gas and proceeded smoothly. Gravimetric analysis of two batches showed that they had an overall As/U ratio of about 1.20. X-ray analysis revealed the presence of only two crystalline phases, UAs₂ and UH₃. Evidently, the temperature was sufficiently low so that the unreacted uranium combined with the released hydrogen to form UH₃. On this basis the following reaction was presumed to have taken place:

Samples of reacted material were heated in vacuum for two hours at 1200°, 1300° and 1400°C to homoge-

⁽⁵⁰⁾ Warren, I. H., *Uranium Compounds as Thermoelectric Materials*, Canadian Mining and Metallurgical Bulletin, **56**, 111 (1963).

45928

FIG. 108. Lattice Constant Versus Composition for the System UAs-US.

nize them and drive off excess arsenic. In each case X-ray analysis revealed a single phase, with the NaCl-type crystal structure exhibited by many actinide compounds. Moreover, the same lattice constant value of $5.779\text{\AA}$ was obtained for material homogenized at the different temperatures. Chemical analyses are presented in Table 55 for two separate batches of UAs calcined at 1400°C . Both materials appeared to be slightly hyperstoichiometric; however, this may not be the case since departure from stoichiometry was only slightly greater than the limits of analytical error. The small amount of oxygen present was tied up in the secondary UO_2 phase, which constituted about 2% of the material.

The UAs powder was dark gray and was not pyrophoric in ambient air. However, as was shown previously,⁽⁵¹⁾ the powder ignited in air at 290°C , exhibiting a very sharp exothermic peak on a DTA thermogram. In this respect and from observations of tarnishing of polished sections, UAs was more susceptible to oxidation than UP. U_3O_8 was the only oxidation product observed on ignition of uranium monoarsenide.

UAs powder calcined at 1400°C yielded a very sharp powder diffraction pattern. The lattice constant value of $5.779\text{\AA}$ corresponds to a theoretical density of 10.79 g/cc for stoichiometric material. Pellets fired at 1800°C had a density of 9.0 g/cc or about 83% of theoretical. One of these pellets, heated in vacuum for four hours at 1800°C , yielded a slightly diffuse diffraction pattern with a lattice constant of $5.777\text{\AA}$. This small reduction in cell size may have resulted from selective loss of arsenic, producing a slight departure from

stoichiometry. A melting point value of $2450^\circ \pm 30^\circ\text{C}$ was obtained for UAs in one atmosphere of helium. Small quantities of metallic uranium were detected in melted samples through X-ray and metallographic examination. Thus, it is likely that the melting point of stoichiometric UAs in equilibrium with its vapor would be still higher. This was shown to be true for UP and was accomplished by sealing stoichiometric material in a gas-tight tungsten crucible.⁽⁵²⁾

UAs exhibited fairly high weight losses in vacuum above 1800°C . At 1900°C pellets of UAs lost approximately four times as much weight as those of either UP or US. Not unexpectedly, UAs powder showed greater weight losses than pellets due to their larger surface area. As was the case with UP, heat-treated powder yielded a much sharper X-ray pattern than that of pellets; however, with UAs the lattice constants of heat-treated pellets and powders were virtually identical.

UAs exhibited complete mutual solubility with UP and US, but no measurable solid solution was observed in the systems UAs-UC and UAs-UN. The relatively small size difference between the arsenic and phosphorus or sulfur atoms and the relatively large size difference between the arsenic and carbon or nitrogen atoms is believed responsible for this behavior.

c. THE SYSTEM UAs-UP (Y. BASKIN)

X-ray and metallographic analysis revealed complete solid solubility in the system UAs-UP. The curve of lattice constant versus composition was linear and conformed almost exactly to Vegard's law. The liquidus curve showed a slight negative deviation from linearity. This could not be accounted for by the presence of free metal in the melted samples, since uranium was observed at all compositional intervals.

d. THE SYSTEM UAs-US (Y. BASKIN)

The system UAs-US also exhibited complete mutual solubility. As shown in Figure 108, the curve of lattice constant versus composition for the system was continuous, but showed a slight positive deviation from a straight line relationship. The liquidus curve was essentially a straight line connecting the end member melting points, in this case, both about 2450°C . While the data suggested a slight positive bulge, it was within the range of experimental error.

e. PHASE STUDIES IN THE PSEUDOBINARY SYSTEM UN-UP (Y. BASKIN)

Phase studies in the pseudobinary system UN-UP have been completed. X-ray diffraction showed no

⁽⁵¹⁾ Annual Report for 1963, Metallurgy Division, ANL-6868, p. 146.

⁽⁵²⁾ Baskin, Y., *Melting Point Determination of UP*, Nucl. Sci. Eng., **24**, 332-335 (1966).

evidence of an intermediate phase in the system. Furthermore, examination of the powder patterns revealed only limited interaction between the compounds. The UP lattice constant, originally 5.589Å, decreased to 5.585Å owing to phosphorus loss at 1800°C,⁽⁵³⁾ and dropped to 5.580Å with addition of UN. A further slight decrease occurred for samples equilibrated at 2000°C. The lattice constant of UN increased slightly from 4.889 to 4.891Å on firing at 1800°C, presumably because of some oxygen solubility in the lattice, but showed no further measurable change with addition of UP. Based on the assumption of a linear relationship between lattice constant and composition approximately 0.7 w/o UN entered the UP lattice at 1800°C, and about 1 w/o at 2000°C. The very limited solid solubility in the system was related to the large size differential between the radii of the nonmetal atoms, 1.57Å for nitrogen and 1.925Å for phosphorus.⁽⁵⁴⁾ This corresponded to a difference of -18.4% when UP was the solvent and +22.6% when UN was the solvent. It is known that substitutional solid solutions of extensive range only occur when the radii of solvent and solute atoms do not differ by more than 14 to 15% of the solvent atom.

Metallographic examination did not reveal any intermediate compound formation. The sample containing 2 w/o UN showed only traces of uranium mononitride, which indicated that between 1 and 2 w/o of the compound entered the UP lattice at 1800°C, and essentially corroborating the results of X-ray analysis.

Results of melting experiments in different atmospheres are summarized in Table 56. Only starting compositions are given, since the melted samples were too small for chemical analysis. A melting-point value of 2820°C was obtained for UN under 2.5 atmospheres of nitrogen, slightly lower than the value of 2850°C reported by Bugl and Bauer,⁽⁵⁵⁾ and Olsen and Mulford.⁽⁵⁶⁾ The disparity might be the result of somewhat higher oxygen content in the present sample. Nitrogen pressures of 2.5 atm or greater were necessary to prevent decomposition of UN and produce congruent melting; use of lower nitrogen pressures resulted in some decomposition and lower melting temperatures. However, use of nitrogen for melting intermediate compositions caused difficulties, since even during the short duration of a melting run nitro-

TABLE 56. MELTING TEMPERATURE DATA IN DIFFERENT ATMOSPHERES

Starting Composition w/o UP	Liquidus Temperature, °C		
	Nitrogen (2.5 atm.)	Helium (1 atm.)	He-N ₂ Mixtures ^(a) (2.5 atm.)
0	2820	2540	2820
14	2785	2465	2730
28	2710	2420	2700
34	2450	2395	—
41	2320	2300	2340
48	2345	2435	2385
58	2330	2460	2385
73	2335	2490	2410
83	2335	2525	2485
95	2390	2550	—
100	2410	2565	2570

^(a) Gas proportions approximated starting compositions, with helium essentially corresponding to UP content and nitrogen to UN content.

gen reacted with the UP component at elevated temperatures, replacing phosphorus in the lattice. The melting temperatures in pressurized nitrogen of UP and compositions rich in UP was significantly lower than in helium, indicating a shift toward higher UN contents in the former atmosphere. The shift in composition was clearly observed in an experiment where UP fragments were heated for 15 minutes at 2000°C in a nitrogen atmosphere; X-ray analysis revealed the formation of moderate amounts of UN. Unfortunately, there was no way of accurately measuring the extent of the compositional shift when samples were melted under pressurized nitrogen.

Elemental phosphorus or phosphine gas were not used as atmospheres owing to safety considerations and the probability of sight-glass fogging by condensing phosphorus. Under these circumstances helium provided the best atmosphere for UP-rich compositions, but was not suitable for the UN-rich portion of the system because considerable decomposition of the nitride occurred. Moreover, close examination revealed that even pressurized helium did not completely suppress decomposition of UP, as shown by the presence of small amounts of uranium in melted samples. Thus, the melting temperature of UP in helium (2565°C) was slightly lower than the melting point value of 2610°C obtained for stoichiometric material sealed in a tungsten crucible.⁽⁵²⁾

Use of helium-nitrogen gas mixtures did not solve the problem; melting temperatures of compositions at the UP end of the system were higher than those in pressurized nitrogen, but lower than those in helium. Evidently, even a small amount of nitrogen was suffi-

⁽⁵³⁾ Baskin, Y., *Properties of Uranium Monophosphide*, J. Am. Ceram. Soc., **49**(10), 541-546 (1966).

⁽⁵⁴⁾ Iandelli, A., *Some Samarium Compounds with the NaCl-Type Structure*, Zeit. anorg. allg. Chem., **288**, 81-86 (1956).

⁽⁵⁵⁾ Bugl, J., and Bauer, A. A., *Phase Relations in the System Uranium-Nitrogen*, J. Am. Ceram. Soc., **47**(9), 425-429 (1964).

⁽⁵⁶⁾ Olsen, W. M., and Mulford, R. N. R., *Decomposition Pressure and Melting Point of Uranium Mononitride*, J. Phys. Chem., **67**(4), 952-954 (1963).

106-8875

Fig. 109. Tentative Phase Diagram of the System UN-UP. The liquidus curve on the UN side of the eutectic is based on samples melted under 2.5 atm N_2 pressure; that on the UP side is based on samples melted under 1 atm He. The join is probably pseudobinary in the system U-N-P and the eutectic at about 2300°C and 40 w/o UP may be a ternary invariant point.

cient to cause an increase in the UN content of samples during melting.

A preliminary phase diagram for the system is presented in Figure 109. The diagram is tentative owing to the use of different atmospheres and the fact that analyses were not made on melted samples. There was no intermediate compound formation and only slight solid solubility of UN in UP. A eutectic occurred at about 2300°C and 40 w/o UP. The system UN-UP is a join in the ternary U-N-P, and the eutectic may well represent a ternary invariant point, possibly, U-UN-UP. The liquidus curve between UN and the eutectic was based on samples melted under 2.5 atm of nitrogen. Since reaction with nitrogen altered the composition of samples containing UP, this part of the curve was probably a bit steeper than it would have been had the compositions remained unchanged. The liquidus curve between the eutectic and UP was based on samples melted under helium and was somewhat depressed as a consequence of dissociation of UP. However, depression of this portion of the liquidus curve was probably limited, since the melting temperature of UP in helium was only 45°C lower than its melting point of 2610°C.⁽⁵²⁾ The solidus temperature was based on observations of initial formation of a liquid phase. The presence in all compositions of about 1% UO_2 was thought to have only minor effect on melting temperatures; it was certainly overshadowed by the atmosphere effect.

3. Electrical Properties and Electronic Configurations of the Actinide Metal Compounds with Nonmetals of Groups IV-VI (O. L. KRUGER AND J. B. MOSER)

a. INTRODUCTION

The actinide elements when alloyed with most of the anion-forming (nonmetal) elements of groups IV, V, and VI combine as MX compounds that have the NaCl-type crystal structure. The thorium, uranium and plutonium compounds are of interest because they have excellent high-temperature properties that make them suitable for fast reactor fuels. Correlation of the properties of these compounds has been a primary effort over the past year. This investigation was initially centered around the electrical properties because it was felt that these properties could best be related to their electronic structures. Good correlation has been obtained and this information is now being used to explain the heat-transport properties.

b. ELECTRICAL PROPERTIES

The actinide monocarbides, mononitrides (mononitrides, monophosphides, monoarsenides and monoan-

timonides), and monochalcogenides (monosulfides, monoselenides and monotellurides) with few exceptions have high electrical and thermal conductivities. Measurements of the electrical resistivity and absolute thermoelectric power of the monocarbide, monophosphide and monosulfide of plutonium reported previously⁽⁵⁷⁾ have shown that the first two compounds are also quasimetallic conductors. Equations for these data, calculated from a least-squares computer program, are given in Table 57. These properties appear to be related according to the equation

$$1/\rho = \sigma = ne\mu \quad (1)$$

where the change in mobility, μ , is indicated by the change in absolute thermoelectric power with temperature. This argument assumes that the effective mass remains constant. Equation (1) seems to be satisfied

⁽⁵⁷⁾ Annual Report for 1965, Metallurgy Division, ANL-7155 p. 106.

TABLE 57. RESISTIVITY AND ABSOLUTE THERMOELECTRIC POWER OF SOME PLUTONIUM IVA TO VIA COMPOUNDS.
 ρ OR $\alpha = a + bT + cT^2 + dT^3 + eT^4$ (298°K TO 1000°K)

Material	Resistivity $-\rho$ (microhm-cm)				Absolute Thermoelectric Power $-\alpha$ (micro V/°K)				
	a	$b \cdot 10^2$	$c \cdot 10^5$	$d \cdot 10^8$	a	$b \cdot 10^2$	$c \cdot 10^5$	$d \cdot 10^8$	$e \cdot 10^{12}$
PuC	263.30	-1.966	-1.171	2.246	-2.43	3.396	-3.445	1.163	—
PuP	644.43	57.317	-78.709	24.895	3.97	2.990	-5.751	1.348	—
PuS	6553	-2112.8	2360.1	-875.7	977.93	-621.22	1257.38	-1061.34	3234.43

for all of the actinide IV to VI nonmetal compounds with the NaCl-type crystal structure, even though these materials have complex band models and their electrical properties could only be correctly described by more complicated equations. Consequently, the values for n (the number of carriers) and μ must represent the sums of these terms for electrons and holes. In metals the carrier concentration usually remains constant over a fairly wide range of temperature, however, the mobility decreases as the mean free path of the carriers decreases with temperature. Although most of the actinide compounds show a similar temperature dependency of the resistivity the increases are much less than that expected from metal theory. On the other hand, our measurements show that the resistivity of PuC is essentially constant from room temperature to 700°C and PuP exhibits a slight decrease in resistivity above about 550°C.⁽⁵⁷⁾ In the case of PuC the invariant resistivity could be due to the defect structure of this material. The defect concentration may be the controlling factor governing the temperature variation of the conductivity in the other compounds as well. However, for these compounds, which have melting points above 2000°C, a nearly constant mean free path below 1000°C does not seem to be an unreasonable assumption which accounts for the relatively temperature insensitive resistivity behavior.

Calculations based on electrical resistivity and thermoelectric power data show that the plutonium compounds and other binary actinide compounds have Fermi energies of 2 to 4 eV and carrier concentrations of 10^{22} cm^{-3} . These values are typical for metallic conductors and they confirm the close relationship between the electrical properties of these compounds and metals.

Evaluation of the data for all of the binary actinide compounds has disclosed a systematic change in resistivity with the position of the nonmetal atom in the periodic table. In Figure 110 the room-temperature electrical resistivities of the compounds are plotted against the atomic number of the actinide components. For a compound of a nonmetal with any given actinide

106-9038

Fig. 110. Room Temperature Resistivities of the Actinide Compounds Plotted Against the Atomic Number of the Actinide Component.

species, substitution of a species of nonmetal atoms from group IV to VI with any other having a higher atomic number increases the resistivity. Likewise, an increase in resistivity occurs when the nonmetal atom does not change and the atomic number of the actinide component increases. The one exception to the quasi-metallic behavior of the actinide compounds in PuS. The data for this compound (Table 57) are plotted as log resistivity versus $1/T$ in Figure 111. Here we see that PuS is an intrinsic semiconductor over the temperature range of 150°C to 425°C with an activation energy for conduction of 0.240 eV. Below 150°C impurities or defects probably govern the conduction

106-8739

Fig. 111. Log Resistivity of PuS versus Reciprocal of the Temperature.

106-8854-Rev. 1

Fig. 112. Cell Volume of NaCl-type Mononitride Compounds as a Function of the Cube of the CN12 Atomic Radii.

mechanism. The carrier concentration changes from $1.6 \times 10^{18} \text{ cm}^{-3}$ at 150°C to $1.2 \times 10^{19} \text{ cm}^{-3}$ at 425°C . Above 425°C degeneracy was observed and Boltzmann statistics can no longer be used for the calculation. The

agreement with theory is good and at higher temperatures carrier concentrations similar to that calculated for the other compounds would be expected.

c. ELECTRON CONFIGURATION

On the basis of available data plutonium monosulfide appears to be the only compound with semiconductor behavior in the group of binary actinide compounds having NaCl-type crystal structures. This deviation from the normal group behavior was unexpected and requires speculation as to what changes have occurred in the bonding to account for this change in properties. Williams⁽⁵⁸⁾ has discussed the nature of the bonding in transition metal carbides which have been studied extensively. Recent theories support the position that these structures are composed of mixtures of covalent and ionic bonds, which result in a complex and little understood type of binding. The actinide compounds (carbides, nitrides, phosphides and sulfides) would be expected to have equally complex structures with covalent and ionic bonds that account for their quasi-metallic conductivities.

In order to get a better understanding of the role of the nonmetal atom in controlling the effective valence of the metal atoms in the various compounds, plots of compound unit cell volume versus the cube of the CN12 metal radius were made for some mononitrides, monophosphides and monosulfides of the rare earths, transition metals and actinides, as shown in Figures 112, 113 and 114. Elements of the rare earth series form NaCl-type compounds when combined with nitrogen, phosphorus and sulfur and can therefore be used for a comparison with the isostructural actinide compounds. The same structure is also found in some transition metal compounds and these have been included in the plots. This type of approach was previously used by Nevitt and Rosen⁽⁵⁹⁾ for the monocarbides. Data needed for computing the compound volumes and metallic radii were obtained from reliable literature sources.⁽⁶⁰⁻⁶³⁾

⁽⁵⁸⁾ Williams, W. S., *Cubic Carbides*, Science, **152**(3718), 34 (1966).

⁽⁵⁹⁾ Annual Report for 1963, Metallurgy Division, ANL-6868, p. 318.

⁽⁶⁰⁾ Gschneidner, K. A., Jr., *Rare Earth Alloys*, D. Van Nostrand Co., Inc., Princeton, New Jersey (1961).

⁽⁶¹⁾ McMasters, O. D., and Gschneidner, K. A., Jr., "Rare Earth Intermetallic Compounds," p. 93 in *Nuclear Metallurgy Vol. X*, International Symposium on Compounds of Interest in Nuclear Reactor Technology, University of Colorado, Boulder (AIME 1964).

⁽⁶²⁾ Storms, E. K., *A Critical Review of Refractories*, LA-2942 (1964).

⁽⁶³⁾ Teatum, E., Gschneidner, K. A., Jr., and Waber, J., *Compilation of Calculated Data Useful in Predicting Metallurgical Behavior of the Elements in Binary Alloys Systems*, LA-2345 (1959).

106-8852

FIG. 113. Cell Volume of NaCl-type Monophosphide Compounds as a Function of the Cube of the CN12 Atomic Radii.

Lattice constants of the uranium and plutonium monophosphides and monosulfides were obtained from compositions that were nonmetal-rich. These compositions were prepared by gas-metal reactions⁽⁶⁴⁾ and homogenized prior to measurement.

Zachariasen⁽⁶⁵⁾ has shown by analogy with elements in the two long periods beginning with Rb and Cs that in the metal structures, thorium, uranium and plutonium have atomic radii corresponding to four, six, and five valence electrons,* respectively. Differences among researchers with regard to the electron distribution between the 7s, 6d, and 5f bands has resulted in controversy concerning the occupancy of the 5f states of the actinides. Zachariasen assumes that there are no electrons present at this level in thorium and uranium but postulates three 5f electrons for plutonium. Katz and Seaborg⁽⁶⁶⁾ propose a fairly regular addition of electrons to the 5f band starting with thorium. Their model postulates three 5f electrons in uranium and six in plutonium.

⁽⁶⁴⁾ Kruger, O. L., and Moser, J. B., *Preparation of the Sulfides and Phosphides of Plutonium*, J. Inorg. Nucl. Chem., **28**, 825 (1966).

⁽⁶⁵⁾ Zachariasen, W. H., "Crystal-Structure Studies of Plutonium Metal," Chap. X, p. 99, *The Metal Plutonium*, University of Chicago Press, Chicago and London (1961).

* Electrons occupying the 6d + 7s energy levels.

⁽⁶⁶⁾ Katz, J. J., and Seaborg, G. T., *The Chemistry of the Actinide Elements*, John Wiley and Sons, Inc., New York (1957).

Plots of the atomic radii⁽⁶⁵⁾ of the actinide metals as a function of atomic number show a decrease to Np and a subsequent increase through Pu to Am. A similar plot was made using compound lattice constants for the actinide monophosphides, monosulfides, monocarbides and mononitrides and is shown in Figure 115. These plots show that a similar relationship exists between atomic radii and atomic number in the actinide com-

106-8853

FIG. 114. Cell Volume of NaCl-type Monosulfide Compounds as a Function of the Cube of the CN12 Atomic Radii.

106-8855

FIG. 115. Lattice Constants of the Actinide Monophosphides, Monosulfides, Monocarbides and Mononitrides Plotted Against the Atomic Number of the Actinide Component.

pound regardless of the nonmetal constituent. This characteristic tends to support the use of the metallic radii predicted by Zachariasen to determine the effective valences of the actinides in these compounds.

The data in Figures 112, 113 and 114 show a consistent relationship between cell dimensions and metal radius for the rare earth compounds which is approximated by a curve that crosses a line connecting the metal radii of the actinides for 3, 4, 5, 6 and 7 valence electrons distributed in the $7s + 6d$ levels. A smaller number of valence electrons appear to be present in the metal constituent of the compound as compared to its metal structure; thorium excepted. In order for the actinide mononitrides to conform to the curve it is necessary for them to have about 4 electrons per atom in the $7s + 6d$ states. Likewise, between 3 and 4 electrons per atom are inferred for the actinide monophosphides and monosulfides. These results appear to be in good agreement with the $4+$ state found by Didchenko and Gortsema⁽⁶⁷⁾ for the metallic component of US, ThS and ThN.

The valence of the actinide constituent appears to be

⁽⁶⁷⁾ Didchenko, R., and Gortsema, F. P., *Magnetic and Electric Properties of Monosulfides and Mononitrides of Thorium and Uranium*, Inorganic Chem., **2**, 1079 (1963).

4. Thermal Conductivity and Heat Capacity of Actinide Compounds

(J. B. MOSER AND O. L. KRUGER)

Significant improvements in the equipment used to determine thermal diffusivity and heat capacity⁽⁶⁸⁾ were made. They consisted in changes of design of the horizontal diffusivity furnace and the incorporation of a laser into the system as shown in Figure 116. Disc-shaped specimens of a number of uranium compounds were prepared as follows: uranium monocarbide by arc melting, uranium monosulfide by cold pressing and sintering, and uranium monophosphide by hot pressing. The specimen characteristics are shown in Table 58. Second phase content ranged from almost zero for arc-cast specimens to 3% by volume for pressed and sintered material. The heat-transport properties and heat capacity of these compounds were then determined between room temperature and 650°C.

The thermal conductivity of the three compounds was calculated from the product of the thermal diffusivity, heat capacity and density and is shown in Figure 117. At room temperature the thermal conductivity

⁽⁶⁸⁾ *Annual Report for 1964, Metallurgy Division, ANL-7000*, p. 106.

about the same for a common nonmetal atom. If this is true, then for each group of compounds, progression from $\text{ThX} \rightarrow \text{UX} \rightarrow \text{PuX}$ would result in a higher density of $5f$ states in the actinide component. The observed changes in the resistivity of the actinide compounds seem to fit this model. Conduction appears to be governed by the carrier concentration in the $s + d$ levels and the scattering that occurs because of $s + d$, f transitions. The low occupancy of f states in ThC, ThN and ThS explains the high electrical conductivities of these compounds (see Figure 110). The higher density of f states in the uranium and plutonium compounds accounts for their higher respective resistivities. In the sulfides a greater degree of ionic bonding would be expected and a separation of f states could then account for the semiconductor properties of PuS.

In view of the above discussion, several other actinide monosulfides may also have semiconductor properties. The two most likely suspects are NpS and AmS, however, the energy separation of the f states in the former compound may be barely detectable. In other compounds of plutonium with group VIA nonmetals (PuSe and PuTe), a greater share of covalent bonding can be expected, therefore, quasimetallic conduction probably occurs.

of the three compounds corrected to theoretical density was found to be 0.057, 0.033, and 0.021 cal $\text{sec}^{-1} \text{ cm}^{-1} \text{ }^\circ\text{C}^{-1}$ for UC, UP, and US, respectively. At 600°C the value for UC decreased to 0.041 cal $\text{sec}^{-1} \text{ cm}^{-1} \text{ }^\circ\text{C}^{-1}$. The thermal conductivity of UP remained equal to its room-temperature value and that of US increased to 0.020 cal $\text{sec}^{-1} \text{ cm}^{-1} \text{ }^\circ\text{C}^{-1}$. The room-temperature heat-capacity values for the three compounds investigated were all slightly above 12 cal $\text{mole}^{-1} \text{ }^\circ\text{C}^{-1}$. At 600°C the heat capacity of UC increased to 15.2 cal $\text{mole}^{-1} \text{ }^\circ\text{C}^{-1}$ whereas no appreciable changes were found for UP and US at this temperature. The experimental specific heat values were used to formulate expressions of the type $C_p = a + bT + cT^{-2}$ with the aid of a computer program. Molar heat capacities, enthalpies and entropies of the compounds were calculated from 127° to 727°C and these values are shown on Table 59.

The electronic contributions to the thermal conductivity (K_e) of the three compounds were calculated by means of the Wiedemann-Franz law from existing elec-

trical conductivity data^(69,70,71) with the Lorenz constant for metallic conductors.

Data of stoichiometric UC were used to calculate K_e , which drops from $0.048 \text{ cal sec}^{-1} \text{ cm}^{-1} \text{ }^\circ\text{C}^{-1}$ at 0°C to 0.042 at 300°C where it remains up to 700°C . Therefore, above 300°C the measured thermal conductivity appears to be entirely electronic in nature. This result is of doubtful validity and a reduction in the Lorenz number due to polar scattering by optical modes seems probable. This type of scattering contributes strongly to the thermal resistance but does not affect the electrical conductivity appreciably. It was found, in the case of TiC,⁽⁷²⁾ that a reduction of 30 to 40 percent in K_e results when this effect is taken into account. In the case of UP the calculated K_e ranged from slightly over 20% of the measured thermal conductivity at room temperature to 60% at 600°C . The values for US were similar and amounted to 30% and 55%, respectively. The subtraction of K_e from the measured thermal conductivity shows that neither of the three compounds observe classic behavior described by the following equation:

$$K = \sigma LT + C/T$$

where the first part is equal to the Wiedemann-Franz law and the second part represents the classic Debye-Peierls lattice contribution to the thermal conductivity. In view of the previous comments on UC and the fact that the lattice component K_e obtained by subtraction varied between 0.02 and $0.01 \text{ cal sec}^{-1} \text{ cm}^{-1} \text{ }^\circ\text{C}^{-1}$ for UP and was close to $0.01 \text{ cal sec}^{-1} \text{ cm}^{-1} \text{ }^\circ\text{C}^{-1}$ for US over the temperature range investigated, the lattice contribution for these compounds was essentially temperature-independent. This type of behavior can be attributed to the fact that point and line defects control the lattice resistance rather than the Umklapp processes involved in traditional heat flow theory. Additional processes such as scattering because of mass differences between metal and nonmetal could also contribute to the lattice resistance. This could be appreciable in compounds of uranium and lighter elements.

⁽⁶⁹⁾ Rough, F. A., and Chubb, W., *Progress in the Development of Uranium Carbide-Type Fuels*, Battelle Memorial Institute Report No. BMI-1554 (1961).

⁽⁷⁰⁾ Warren, I. H., and Price, C. E., *Thermoelectric Properties of Cubic Uranium Monocompounds*, Can. Met. Quart., **3**, 183-196 (1964).

⁽⁷¹⁾ Tetenbaum, M., *Thermoelectric Properties of Uranium Monosulfide, Thorium Monosulfide, and US-ThS Solid Solutions*, J. App. Phys., **35**, 2468-2472 (1964).

⁽⁷²⁾ Williams, W. S., *High-Temperature Thermal Conductivity of Transition Metal Carbides and Nitrides*, J. Am. Ceram. Soc., **49**, 156-159 (1966).

Fig. 116. Thermal Diffusivity Apparatus.

TABLE 58. SPECIMEN CHARACTERISTICS OF URANIUM COMPOUNDS

Compound	Uranium Monocarbide	Uranium Monosulfide	Uranium Monophosphide
Method of preparation	Arc melting	Cold pressing & sintering at 1800°C	Hot pressing at 1400°C
Density % of theoretical	>99	93	93
Second phase % by volume	0	3	1
Wt. % Oxygen	0.005	0.3	0.13
Wt. % Nitrogen	—	—	0.09

In order to obtain K_l by a different approach the values of the electrical conductivities of UC, US, and UP at 600°C were plotted versus the thermal conductivities at the same temperature in Figure 118. This curve was then projected backward to zero electrical conductivity. Its intersection with the abscissa yielded a value of $0.02 \text{ cal sec}^{-1} \text{ cm}^{-1} \text{ }^\circ\text{C}^{-1}$ as an approximation of K_l^{UX} with the rock-salt structure. This value agrees rather well with the experimental value obtained by subtracting K_e from K for US and UP. A number of assumptions have to be made in this semi-quantitative approach, one of them being that the elastic constants and sound-velocities of the three compounds are similar. It has been verified that these parameters are indeed similar in the compounds under

106-8748-Rev. 1

Fig. 117. Thermal Conductivity of Uranium Monocarbide, Monophosphide and Monosulfide.

TABLE 59. MOLAR THERMODYNAMIC PROPERTIES OF URANIUM COMPOUNDS

$T^{\circ}\text{K}$	C_p (Cal mole ⁻¹ °K ⁻¹)	$H_T - H_{298}$ (Cal mole ⁻¹)	$S_T - S_{298}$ (Cal mole ⁻¹ °K ⁻¹)
Uranium Monosulfide US(s)			
$C_p = 12.12 + 7.107 \times 10^{-4} T - 1.781 \times 10^3 T^{-2}$ (298°-1000°K)			
400	12.4	1260	3.6
500	12.5	2500	6.4
600	12.5	3750	8.7
700	12.6	5010	10.6
800	12.7	6270	12.3
900	12.8	7550	13.8
1000	12.8	8830	15.2
Uranium Monophosphide UP(s)			
$C_p = 12.10$ (298°-1000°K)			
400	12.1	1230	3.6
500	12.1	2440	6.3
600	12.1	3650	8.5
700	12.1	4860	10.3
800	12.1	6070	11.9
900	12.1	7280	13.4
1000	12.1	8490	14.6
Uranium Monocarbide UC(s)			
$C_p = 12.32 + 3.329 \times 10^{-3} T - 1.130 \times 10^5 T^2$ (298°-1000°K)			
400	12.9	1280	3.7
500	13.5	2600	6.6
600	14.0	3980	9.1
700	14.4	5400	11.3
800	14.8	6860	13.3
900	15.2	8360	15.1
1000	15.5	9900	16.7

106-9033

Fig. 118. Isothermal Plot of Thermal versus Electrical Conductivity of Uranium Compounds.

consideration.^(73,74) Another assumption is that electron-phonon interactions are of the same type in all three compounds but this may be questionable because of differences between the band-structures.

In order to compare the above extrapolation with the lattice thermal conductivity due to anharmonic processes only, a calculation was made based on the Leibfried and Schlömann equation.⁽⁷⁵⁾ This yielded a value

⁽⁷³⁾ Kempter, C. P., *The Isothermal Compressibility of Uranium Monocarbide*, J. Less-Com. Met., **10**, 294-295 (1966).

⁽⁷⁴⁾ Tottle, C. R., *Mechanical Properties of Uranium Compounds*, ANL-7070 (1965).

⁽⁷⁵⁾ Leibfried, G., and Schlömann, E., *Heat Conduction in Electrically Insulating Crystals*, Akad. Wiss. Göttingen, Math.-Physik. Kl., **IIA**, 71 (1954).

45001

FIG. 119. Thermal Conductivity of UO_2 as a Function of Temperature.

of $K_l = 0.04 \text{ cal sec}^{-1} \text{ cm}^{-1} \text{ }^\circ\text{C}^{-1}$ for uranium monocarbide. The equation used does not consider all types of U-processes in detail and other approximations are employed as well. Also, the use of the third power of

the Debye temperature in this equation is likely to introduce some inaccuracy in the calculation. The value of K_l calculated from the Leibfried and Schlömann equation is likely to be higher than that obtained from the Wiedemann-Franz law. This was found to be the case here and substantiates the argument in favor of a predominance of defect scattering over anharmonic processes in the compounds investigated.

Thermal diffusivity measurements have been extended to temperatures close to 1500°C by the use of the new laser in conjunction with a tantalum heater furnace.⁽⁷²⁾ A lead sulfide detector in a photoelectric cell is employed as a temperature-sensing device between 300°C and 1500°C . Measurements in this temperature range have been carried out on uranium dioxide and the results are shown in Figure 119 as a plot of thermal conductivity versus temperature. Although there is still considerable scatter, good agreement between ANL data and literature values⁽⁷⁶⁾ have been obtained.

⁽⁷⁶⁾ Godfrey, T. G., Fulkerson, W., Kolhe, T. G., Moore, J. P., and McElroy, D. L., *Thermal Conductivity of Uranium Dioxide from -57° to 1100°C by a Radial Heat Flow Technique*, J. Am. Ceram. Soc., **48**, 297-305 (1965).

5. (Th-U-Pu) Phosphide Bodies (Y. BASKIN)

Studies were conducted on the high-temperature compatibility of UP with the following refractory metals: Ti, Zr, Nb, Ta, Mo and W. UP powder was blended with 50 a/o of each of the metal powders and ball-milled for five hours. Pellets were fabricated using stearic acid binder and fired in vacuum for two hours at temperatures ranging from 1600°C to 2200°C .

Results of X-ray and metallographic examinations of UP compatibility specimens are presented in Table 60. Titanium reacted moderately with UP at 1600°C , but the pellets melted completely at 1800°C . Titanium did not displace uranium from the UP lattice at 1600°C ; however, the lattice parameter value of $5.54\text{\AA}$ for the UP phase indicated that a significant amount of titanium entered into solid solution at 1800°C , displacing uranium. The unidentified phase was presumed to be a titanium phosphide, but was not TiP. Metallic uranium probably was also produced as a concomitant of the formation of a titanium-phosphorus compound.

Zirconium exhibited substantial reaction with UP at 1600°C , characterized by appreciable solid solution and formation of uranium and an unidentified phase. Solid solution was even more extensive at 1800°C , and

the pellets were partially melted. Metallic uranium and the same unidentified phase were observed in samples heated at 1800°C .

Moderate reaction occurred between niobium and UP at 1800°C , and resulted in the formation of a liquid intergranular zone containing niobium and an unidentified phase. Additional melting occurred at 2000°C along with appreciable vaporization. The same unidentified phase was observed at 2000°C , but there was no sign of niobium metal. The relatively large lattice constant of UP indicated that little or no niobium entered into solid solution.

Tantalum exhibited only slight reaction with UP at 1800°C and 2000°C , but the pellets melted at 2200°C . X-ray diffraction analysis of samples fired at 1800°C and 2000°C revealed unalloyed UP, tantalum and an unidentified phase. Only UP and tantalum were observed in the melted material (2200°C).

Pellets containing molybdenum and tungsten exhibited no reaction at 1800°C . The composition of UP-Mo showed incipient melting and vaporized considerably at 2000°C . X-ray analysis revealed an unidentified phase along with unalloyed UP and molybdenum.

TABLE 60. HIGH-TEMPERATURE COMPATIBILITY OF UP-METAL MIXTURES

Temperature (°C)	Metal	Phases Observed	Lattice Constant of UP Phase (Å)	Remarks
1600	Ti	UP, U, UIPh	5.586	Moderate reaction.
	Zr	(U,Zr)P, U, UIPh	5.50	Moderate reaction.
1800	Ti	(U,Ti)P, U, UIPh	5.54	Pellets melted.
	Zr	(U,Zr)P, U, UIPh	5.45-5.48	Pellets partially melted.
	Nb	UP, UIPh	5.585	Moderate reaction, some melting.
	Ta	UP, Ta, UIPh	5.586	Slight reaction.
	Mo	UP, Mo	5.586	NR
	W	UP, W	5.586	NR
2000	Nb	UP, UIPh	5.585	Some melting and vaporization.
	Ta	UP, Ta, UIPh	5.585	Slight reaction.
	Mo	UP, Mo, UIPh	5.584	Some melting and considerable vaporization.
	W	UP, W	5.584	NR
2200	Ta	UP, Ta	5.584	Pellets melted.
	W	UP, W	5.584	NR

Note: UIPh = Unidentified Phase(s); NR = No Reaction.

TABLE 61. LIQUIDUS TEMPERATURES OF UP-METAL COMPOSITIONS

Composition	Liquidus Temperature (°C)	Melting Point of Metal (°C)
UP-Zr	2055	1852
UP-Ti	2110	1668
UP-Nb	2380	2468
UP-Mo	2395	2610
UP-Ta	2405	2996
UP-W	2575	3410

TABLE 62. VAPORIZATION BEHAVIOR OF UP IN VACUUM

	Pellet with 1% Binder	Pellet without Binder	Powder with 1% Binder	Powder without Binder
A. 4 hrs at 2000°C w/o loss Lattice constant, A	12.2 5.586	11.2 5.586	21.2 5.588	19.8 5.588
B. 4 additional hrs at 2000°C w/o loss Lattice constant, A	9.2 5.585	9.7 5.585	17.8 5.588	17.7 5.588

Note: Original material had a lattice constant of 5.589Å.

Tungsten showed no sign of reaction with UP at 2200°C. The lattice constant of UP indicated that little or no tungsten entered the rock-salt structure at that temperature.

Fragments of the UP-metal mixtures were heated rapidly in a tungsten-wedge furnace to obtain the liquidus temperature data shown in Table 61. The liquidus temperatures represented complete melting of the compositions, and, in some cases were considerably higher than the temperatures at which melting was noted in the previous runs. Nevertheless, these results paralleled the compatibility observations presented in Table 60. Interestingly, the liquidus temperatures of the UP-metal mixtures generally followed the order of melting points of the pure metals.

Heating of UP pellets in vacuum above 1400°C generally resulted in decreased lattice constants, which accompanied a selective loss of phosphorus.⁽⁷⁷⁾ Reduction in cell size with the loss of the relatively large phosphorus atoms suggested formation of anion lattice vacancies. The UP lattice parameter, which was 5.589Å for stoichiometric material fell to a minimum value on heating between 2000°C and 2100°C. However, the trend was reversed when pellets were heated at still higher temperatures, with the lattice parameter approaching the original value when heat treatment was carried out about 2400°C. The lowest lattice parameter value observed was 5.584Å, corresponding to a P/U ratio of approximately 0.95. Thus, the homogeneity range of UP was greatest at about 2050°C but fell off markedly both at lower and higher temperatures. Magnier and Accary⁽⁷⁸⁾ found a similar phenomenon with UC; namely, a maximum solubility of uranium in UC at 1700°C, with very low solubility at temperatures lower than 500°C, or higher than 2100°C.

Recent experiments revealed that there was a difference between the vaporization behavior of UP pellets and powder at 2000°C (see Table 62). As might be expected, weight losses from powders were considerably greater than those from pellets, due to the larger surface areas presented by the former. Surprisingly, however, the lattice parameter of the powders was very little changed from that of the original material, while those of the pellets exhibited significant decreases. Apparently, loss of phosphorus by the powder was nearly balanced by loss of uranium, indicating that UP vaporized almost congruently at 2000°C, whereas phos-

⁽⁷⁷⁾ Baskin, Y., *Properties of Uranium Monophosphide*, J. Am. Ceram. Soc., **49**(10), 541-546 (1966).

⁽⁷⁸⁾ Magnier, P., and Accary, A., "The Solubility of Uranium in Uranium Monocarbide," *Proceedings of the Symposium on Carbides in Nuclear Energy*, Vol. I, p. 23-32, MacMillan and Co., Ltd. (1964) London.

phorus was clearly selectively lost from the pellets at this temperature. The pellets had a density of 93% of theoretical, with very little open porosity; consequently, most of the vaporization came from pellet surfaces. Movement of atoms from the pellet interior to the surface would be mainly through some diffusion

process, and the relatively low lattice constant exhibited by the pellets suggested that diffusion of phosphorus in UP was more rapid than that of uranium. The presence of binder did not appear to have had any effect on the vaporization behavior; chemical analysis did not reveal any carbon residue in the samples.

6. Mechanical Properties of Uranium Compounds

(J. H. HANDWERK, R. J. BEALS, AND G. M. DRAGEL)

The mechanical testing of uranium dioxide under four point-loading was continued. Specimens were loaded to failure at 25°C and, at 125°C intervals, from 1000°C to 1900°C.

The results obtained in this study do not correlate completely with previously reported data.⁽⁷⁹⁾ The testing machine was recalibrated and the operation of the

All tests were carried out in vacuum on specimens that had been sintered in hydrogen at 1750°C for four hours. After sintering and prior to testing, specimens were stored in vacuum desiccators. For the elevated temperature tests, specimen temperature was increased by 20°C per minute, then held for at least 20 minutes at test temperature before the load was applied.

TABLE 63. MECHANICAL PROPERTIES OF UO_2 AT 25°, 1000°, 1125°, 1250° AND 1375°C IN VACUO

Number of Specimens	Density (g/cc)		Modulus of Rupture (kg/cm ²)		Mean Load Rate (g/sec)	Mean Total Strain (mm)	Temp. (°C)	Remarks
	Mean	Standard deviation	Mean	Standard deviation				
3	10.65	0	1289	118.4	32.1	0.224	25	Slow Strain
3	10.65	0	1189	222.1	156.6	0.205	25	Medium Strain
3	10.65	0	1320	241.9	477.3	0.182	25	Fast Strain
6	10.65	0.010	1676	166.8	58.2	0.31	1000	Slow Strain
6	10.68	0.029	1756	276.5	229.7	0.26	1000	Medium Strain
6	10.64	0.007	1403	207.9	487.6	0.23	1000	Fast Strain
6	10.71	0.019	1451	73.9	52.2	0.24	1125	Slow Strain
5	10.71	0.008	1914	219.3	263.1	0.29	1125	Medium Strain
4	10.73	0.005	1604	94.8	528.4	0.26	1125	Fast Strain
6	10.64	0	1589	237.8	56.1	0.25	1250	Slow Strain
9	10.64	0.023	1669	182.5	198.9	0.23	1250	Medium Strain
6	10.63	0.003	1712	245.3	496.6	0.22	1250	Fast Strain
5	10.73	0.006	1408	62.8	29.0	0.52	1375	Slow Strain
5	10.72	0.008	1540	69.2	164.2	0.32	1375	Medium Strain
5	10.73	0.009	1448	118.1	452.7	0.26	1375	Fast Strain

machine was changed somewhat. The sintered densities of the test specimens in the current tests were higher than those in the earlier work.⁽⁷⁹⁾ Mean strain rates at the slow, medium and fast load applications were not identical between the tests as shown in Tables 63 and

There was little difference in the maximum fiber stress for the different strain rates for uranium tested at 25°C, as may be seen in Figure 120 and in Table 63. The values of modulus of rupture were between 1189 and 1320 kg/cm². There was an increase in strength in the material between room temperature and 1000°C for all strain rates. The increase was greatest for the medium strain rate and least for the fast rate. The

4.

⁽⁷⁹⁾ Annual Report for 1965, Metallurgy Division, ANL-7155, pp. 111-116.

TABLE 64. MECHANICAL PROPERTIES OF UO_2 AT 1500°, 1625°, 1750° AND 1900°C IN VACUO

Number of Specimens	Density (g/cc)		Modulus of Rupture (kg/cm^2)		Mean Load Rate (g/sec)	Mean Strain Rate (mm/sec $\times 10^{-4}$)	Mean Total Strain (mm)	Temp. ($^{\circ}\text{C}$)	Remarks
	Mean	Standard deviation	Mean	Standard deviation					
5	10.66	0.008	1384	40.9	20.5	1.60	0.61	1500	Slow Strain
6	10.67	0.009	1448	222.9	143.3	6.50	0.353	1500	Medium Strain
5	10.67	0.006	1555	135.9	389.8	16.9	0.36	1500	Fast Strain
5	10.62	0.004	1558	291.9	426.7	16.7	0.34	1500	Fast Strain
6	10.72	0.035	970	54.7	7.03	3.86	3.00	1625	Slow Strain
7	10.74	0.029	1138	88.7		11.9	2.00	1625	Medium Strain
7	10.72	0.021	1227	99.8	168.2	24.6	0.90	1625	Fast Strain
5	10.63	0.006	496	49.6	3.17	2.92	3.35	1750	Slow Strain
5	10.62	0.006	1021	113.9	28.2	11.7	2.47	1750	Medium Strain
5	10.63	0	1355	102.8	144.9	25.7	1.34	1750	Fast Strain
5	10.66	0.006	658	50.4	13.5	11.8	3.10	1900	Medium Strain
5	10.65	0.006	849	64.8	44.8	30.3	3.10	1900	Fast Strain

106-9292-A

FIG. 120. Maximum Stress vs Temperature of High-density UO_2 for Three Strain Rates.

Fig. 121. Total Strains vs Temperature of High-density UO_2 for Three Strain Rates.

106-9292-B

maximum fracture stress occurred at 1000°C for the slow rate, at 1125°C for the medium strain rate and at 1250°C for the fast strain rate. There was little deflection in any of the specimens until test temperatures in excess of 1250°C were used (see Figure 121). The strength of the specimens generally decreased, in a sawtooth fashion, above 1250°C .

The highest maximum fiber stress recorded during this study occurred at 1125°C under a medium strain rate (263 g/sec), yielding a modulus of rupture of 1915 kg/cm². There was little evidence of plastic deformation with a mean total strain of 0.29 mm. The lowest maximum fiber stress occurred at 1750°C at the lowest strain rate of 50 g/sec when a modulus of 496 kg/cm² was calculated.

The deformation behavior changes markedly in the brittle-to-ductile region. Table 62 shows the data in the brittle region while Table 63 shows the data in the ductile region. Some changes in deflection are noted between 1250°C and 1375°C for the slow strain rate but the largest change occurs above 1500°C . Similar behavior was noted for the higher strain rates.

Load deflection curves show an initial elastic portion after which a yield point is observed in most specimens tested at 1000°C and above. In some tests, the load deflection curve has a well-defined yield point while in others there is only a change in slope from the initial part of the curve. Generally, the yield point is followed, with further application of load, by a rise to maximum fiber stress, where failure occurs. At temperatures above 1625°C , the yield point is followed by an increase to maximum stress but it drops in value before failure. Serrated yielding was often observed at elevated temperatures, particularly at the slow strain rate.

The density of the specimens changed only slightly during testing. The greatest density decrease was observed at 1900°C under medium strain. The immersion density changed by 0.5% when measurements were taken with liquids of CCl_4 and mercury. With the high sintered densities of the specimens tested, porosity played a smaller role in the overall behavior of the material than had been observed in earlier tests with lower densities.

E. DEVELOPMENT OF THORIUM-URANIUM AND THORIUM-URANIUM-PLUTONIUM FUELS (B. BLUMENTHAL AND D. R. O'BOYLE)

1. Introduction

Because of the high melting point (1725°C) of thorium and the isotropic structure of the alpha and beta allotropes, thorium-base alloys are of interest as fast reactor fuels. Early work on the irradiation behavior of thorium-uranium alloys⁽⁸⁰⁾ showed that binary thorium-base alloys behave well under irradiation. The excellent irradiation stability of binary Th-U alloys is believed due to the isotropic structure of both the face-centered cubic alpha phase (stable between room temperature and 1365°C) and the body-centered cubic beta phase (stable between 1365°C and 1725°C). Recent work on Th-Pu and Th-U-Pu alloys has established the phase relations in the binary and ternary alloys systems. Previously, work on thermal expansion, fabricability, and compatibility with jacketing materials has been reported.^(81,82) Details of the

phase studies in the ternary Th-U-Pu system are reported by Blumenthal, *et al.*⁽⁸³⁾

During the past year, irradiation experiments have been initiated on thorium-20 w/o uranium, Th-10w/oU-10w/oPu, and Th-20w/oU-10w/oPu alloys jacketed in V-20w/oTi. These compositions were chosen on the basis of earlier studies that showed these alloys had a solidus temperature above 1000°C and were compatible with V-20w/oTi. The irradiations are being performed in instrumented capsules in CP-5 at maximum jacket temperatures between 610°C and 630°C, and as of January 1, 1967, the burnup is approximately 7×10^{20} fissions/cc. In addition to the phase studies and irradiation tests, thermal conductivity and thermal cycling behavior were measured on the ternary alloys of interest as fast reactor fuels and are reported below.

⁽⁸⁰⁾ Kittel, J. H., Horak, J. A., Murphy, W. F., and Paine, S. H., *Effects of Irradiation on Thorium in Thorium-Uranium Alloys*, ANL-5674 (1963).

⁽⁸¹⁾ *Annual Progress Report for 1964, Metallurgy Division*, ANL-7000, 69-70.

⁽⁸²⁾ *Annual Progress Report for 1965, Metallurgy Division*, ANL-7155, 97-100.

⁽⁸³⁾ Blumenthal, B., Sanecki, J. E., and Busch, D. E., *Thorium-Uranium-Plutonium Alloys as Potential Fast Power Reactor Fuels Part I. Th-U-Pu Phase Diagram*, ANL-7258.

2. Thorium-Plutonium Phase Studies

Lattice-parameter measurements for binary Th-Pu alloys containing up to 60 a/o plutonium are shown in Figure 122. These data were obtained with the use of needle specimens approximately 0.4 mm in diameter and 8 mm in length, quenched from 700°C and from 900°C. All lattice parameters were obtained with an 11.46 cm Philips camera and with nickel-filtered CuK α radiation. The lattice parameters were calculated for the wave lengths of CuK α_1 = 1.54051Å and CuK α_2 = 1.54433Å and with application of the Nelson-Riley extrapolation function. A least-square extrapolation was carried out with an IBM 704 computer and the program of Mueller and Heaton.⁽⁸⁴⁾ These data show that at 700°C the solid solubility of plutonium in α -thorium extends to 48 a/o plutonium and that at 900°C the solid solubility limit decreases to 42 a/o plutonium. This study corroborates the work of Poole, Williamson

106-9151

FIG. 122. α_{Th} Lattice Parameter vs Composition of Binary Th-Pu Alloys.

⁽⁸⁴⁾ Mueller, M. H., and Heaton, L. R., *Determination of Lattice Parameters with the Aid of a Computer*, Acta Cryst. **13**, 828-829 (1960).

and Marples,⁽⁸⁵⁾ whose results are also shown in Figure 122. Early work on the Th-Pu phase diagram by Bochvar⁽⁸⁶⁾ suggested that beta thorium is stabi-

⁽⁸⁵⁾ Poole, D. M., Williamson, G. K., and Marples, J. A. C., *Preliminary Investigation of the Plutonium-Thorium System*, J. Inst. Met. **86**, 172-176 (1957/1958).

⁽⁸⁶⁾ Bochvar, A. A., Konobeevsky, S. T., Kutaitsev, V. I., Menskitova, I. S., and Chevatarev, N. T., *The Interaction Between Plutonium and Other Metals in Connection with Their*

lized by plutonium down to 600°C. This investigation found that only alpha-thorium is stable below 900°C as indicated by X-ray diffraction (Figure 122), differential thermal analysis (DTA), electrical resistivity, and dilatometric measurements.⁽⁷⁸⁾ Thus, the Th-Pu diagram proposed by Poole, *et al.*,⁽⁸⁴⁾ is supported by this investigation.

Arrangement in Mendeleev's Periodic Table, Proc. 2nd Geneva Conf. **6**, 184-193 (1958).

3. Thorium-Uranium-Plutonium Phase Studies

Twenty-four Th-U-Pu alloys were investigated by means of DTA, metallography, dilatometry, X-ray diffraction and electron microprobe analysis. Study of a series of alloys containing 2 a/o uranium showed that the solubility of uranium in the Th-Pu phases is less than 2 a/o. Electron microprobe analysis of ternary alloys showed that the alpha thorium phase is in equilibrium with phases of the U-Pu binary system. No ternary Th-U-Pu intermediate phases were found. Small uranium additions to binary Th-Pu alloys containing more than 10 a/o plutonium, had a strong effect on reducing the solidus temperature. A series of alloys were prepared containing 2 a/o and 4 a/o uranium and with plutonium contents from 0 to 60 a/o. Lattice parameter measurements of alloys in this series quenched from 700 and 900°C established the boundary between the α -Th + α -U two phase region and the α -Th + γ U + liquid three phase region. These boundaries are shown in the 900°C isothermal section presented in Figure 123. At lower temperatures, the α -Th + γ U + liquid three phase region moves toward the Th-Pu side of the diagram. At 760°C the γ U + β U + α Th three phase region enters the ternary system from the Th-U side and transforms by a Class III peritectoid reaction to η U + Pu at 714°C.

A proposed scheme of reactions involving the liquid in the Th-U-Pu system is shown in Figure 124. In the scheme it is assumed that beta Th + liquid peritectically form α Th at about 1390°C and that the α Th + β Th + liquid three-phase region crosses the thorium corner and exists from the ternary system as the eutectic reaction β Th $\rightarrow$ α Th + liquid at 1265°C. As previously indicated, the α Th + γ U + liquid three-phase region crosses from the Th-U side of the diagram to the Th-Pu side where it peritectically forms the $\text{Pu}_2\text{Th}_{(1-x)}$ intermediate phase at 630°C. Two of the resultant three-phase regions (α Th + liquid + compound and liquid + ϵ Pu + compound) exit from the system in the U-Pu binary at 615°C and

605°C, respectively. The temperature for the Class-III formation of the Th-Pu intermediate phase at 630°C was indicated by dilatometry and by DTA.

Solid-state reactions that occur in the Th-U-Pu system are shown in Figure 125. Three different isothermal four phase reactions were found at 714°C, 610°C and 595°C. As indicated in Figure 124, these isothermal reactions correspond to α Th + β U + γ U $\rightarrow$ eta, α Th + β U + eta $\rightarrow$ zeta and α Th + β U $\rightarrow$ α U + zeta. Below 595°C the α Th + α U + zeta three-phase region is stable to room temperature. Alloys of interest as fast reactor fuels containing less than 10 a/o plutonium lie in the α Th + α U two-phase region at temperatures below 595°C.

An isoplethal section through the ternary system at 10 a/o plutonium is shown in Figure 126. The transformation temperatures indicated were determined by DTA and dilatometry. The limited solubility of uranium in α -thorium at 700°C and 900°C is clearly

FIG. 123. Th-U-Pu 900°C Isotherm.

106-9124

FIG. 124. Th-U-Pu System Scheme of Reactions Involving the Liquid.

* The symbols γ_U and ϵ_{Pu} are interchangeably used for the continuous series of bcc solid solutions between γ_U and ϵ_{Pu} .

** C designates the intermediate phase $Pu_2Th_{(1-x)}$.

106-8906

FIG. 125. Th-U-Pu System Solid State Reactions in Intermediate Temperature Range.

106-9143

FIG. 126. Th-U-Pu System Isopleth at 10 *a/o* Plutonium.

indicated. As shown in the figure, the solidus temperature is reduced from about 1300°C in the binary Th-Pu system to approximately 900°C with the addi-

tion of 2 *a/o* uranium. Solidus temperatures of alloys containing 10 and 20*a/o* uranium are 917°C and 955°C, respectively.

4. Thermal Conductivity and Thermal Cycling of Th-U-Pu Alloys

Thermal conductivities of two Th-U-Pu alloys were measured between 100°C and 800°C by comparison with an Armeo iron standard. These data are shown in Table 65. A least squares fit of the data gave the following expressions for thermal conductivity that are valid between 273°K and 1073°K.

$$\begin{aligned} \text{Alloy} \\ \text{Th-10U-10Pu } K \left(\frac{\text{watts}}{\text{cm} \cdot ^\circ\text{C}} \right) &= 0.4371 - 67.95T^{-1} - 3.007 \times 10^{-5}T \\ \text{Th-20U-10Pu } K \left(\frac{\text{watts}}{\text{cm} \cdot ^\circ\text{C}} \right) &= 0.4451 - 83.79T^{-1} - 1.541 \times 10^{-5}T \end{aligned}$$

TABLE 65. THERMAL CONDUCTIVITY OF TH-10*w/o*U-10*w/o*Pu AND TH-20*w/o*U-10*w/o*Pu ALLOYS (watts/cm·°C)

Temp. (°C)	Th-10U-10Pu	Th-20U-10Pu
100	0.232	0.215
200	0.279	0.261
300	0.301	0.290
400	0.316	0.310
500	0.326	0.325
600	0.333	0.336
700	0.338	0.344
800	0.342	0.351

Ternary alloys of the same composition were thermally cycled 100 times in NaK between 450°C and 800°C. The Th-20U-10Pu alloys showed a slight in-

crease in density (+0.05%) with a slight increase in length, while the Th-10U-10Pu alloys showed a slight decrease in density (−0.01%).

5. Irradiation of Th-U and Th-U-Pu Fuels

Six Th-U and Th-U-Pu fuel alloys jacketed in V-20w/oTi tubing are being irradiated in the CP-5 reactor. The specimens are being irradiated at maximum jacket temperatures of 590°C and have reached a maximum 15.8 *a/o* (U + Pu) burnup. The objectives of the experiment are to determine the relative swelling behavior of the fuels, the restraint characteristics

of the jacket and the maximum attainable burnup before jacket failure. Neutron radiographs of these specimens at 13.3 *a/o* burnup showed that the Th-U pins had not elongated whereas the Th-U-Pu pins had elongated an average of 8%. Additional details on the design of the fuel specimens and the irradiation conditions are summarized in Table 66.

TABLE 66. STATUS OF METAL FUEL IRRADIATIONS IN PROGRESS—CP-5 REACTOR

Test Reactor	Capsule or S/A No.	Specimen Number	Design Parameters					Operating Conditions			
			Fuel composition, w/o	Effective density, %	Cladding composition, w/o	Cladding OD, in.	Clad thick., in.	Max. kw/ft	Max. clad. Temp., °C	Burnup to Date	
										<i>a/o</i> , U + Pu	fiss/cc × 10 ⁻²⁰ ⁽¹⁾
CP-5	CP-50	1N16	Th-20U	75	V-20Ti	0.196	0.015	8.7	590	13.6	6.5
CP-5	CP-50	4N19	Th-20U	75	V-20Ti	0.196	0.015	8.7	560	13.6	6.5
CP-5	CP-50	2N17	Th-10Pu-10U	75	V-20Ti	0.196	0.015	9.2	590	15.8	7.4
CP-5	CP-50	5N20	Th-10Pu-10U	75	V-20Ti	0.196	0.015	9.2	590	15.8	7.4
CP-5	CP-50	3N18	Th-10Pu-20U	75	V-20Ti	0.196	0.015	8.7	560	9.2	6.7
CP-5	CP-50	6N21	Th-10Pu-20U	75	V-20Ti	0.196	0.015	8.7	560	9.2	6.7

⁽¹⁾ Based on effective density.

F. EXPERIMENTAL IRRADIATIONS OF FUELS AND STRUCTURAL MATERIALS

1. Irradiation of Uranium Sulfide (Y. K. YOON)

The irradiation program on uranium sulfide is continuing with the goal of achieving 10 *a/o* burnup (22×10^{20} fission/cc). Two instrumented capsules containing eight specimens of 6.42 mm (0.253 in.) diameter US pellets in 0.305 mm (0.012 in.) thick Nb-1w/oZr jackets remain under irradiation in the MTR.

Estimated burnups of from 4.5 to 7.4 *a/o* (9.0 to 16.0×10^{20} fission/cc) had been achieved by the end of 1966. Jacket surface temperatures in the respective capsules are in the ranges of 550°C to 650°C and 700°C to 750°C.

2. Irradiation of Paste Fuels (R. CARLANDER)

Investigation of the paste-fuel concept, which combines the advantages of metallic fuels of high thermal conductivity and ceramic fuels of high irradiation stability, was the subject of a joint experiment by United Nuclear Corporation and Argonne National Laboratory. ANL's part in the project has been completed. UNC utilized the paste-fuel concept by developing, characterizing, and fabricating a prototype paste-fuel element consisting of a 50:50 mixture by volume of sodium and 10μ UO_2 particles, 20% enriched, jacketed in AISI Type 304 stainless steel. ANL encapsulated and irradiated the fuel element in MTR

to approximately 1% burnup of the uranium atoms at a jacket temperature in the range of 600°C. The determination of fission-gas release and possible fuel redistribution during irradiation were important goals of the experiment.

The prototype fuel element, designated ANL-55-9, had a fuel-column height of 9 inches and was approximately 18 inches in overall length. Thermocouples were attached to the surface of the 0.375-inch-OD, 0.020-inch-wall Type 304 stainless steel near the center and at the top of the fuel column and $\frac{1}{4}$ inch, $\frac{3}{4}$ inch, and $4\frac{1}{8}$ inches from the top of the fuel column

FIG. 127. ANL-55-9 Paste Fuel Element Temperatures. MTR Cycle 241, 4/8/66-4/14/66.

in order to detect possible fuel movement during irradiation. The fuel element was irradiated during MTR cycles 241 through 247.

Temperature profiles of the stainless steel jacket at the various thermocouple locations were plotted for seven-day periods during Cycle 241 (Figure 127) when the capsule was inadvertently inserted in the wrong position. The profiles for Cycle 242 (Figure 128) are also representative of Cycle 243. The profiles for Cycle 244 (Figure 129) are likewise representative of Cycle 247. The temperature profiles indicate that al-

though there was no volume expansion of the fuel during Cycles 241 to 243, the fuel column did appear to rise as expected during Cycles 244 to 247 immediately after approximately 0.5% burnup of the uranium atoms had been obtained.

The postirradiation examination of the fuel element, however, did not substantiate the indication of volume expansion of the fuel after 0.5% burnup. Neutron radiographs of the fuel element revealed that the paste fuel redistributed during irradiation into small clusters within the stainless steel jacketing (Figure

FIG. 128. ANL-55-9 Paste Fuel Element Temperatures. MTR Cycle 242, 5/1/66-5/7/66

FIG. 129. ANL-55-9 Paste Fuel Element Temperatures. MTR Cycle 244, 6/15/66-6/21/66

FIG. 130. Neutron Radiographs of Paste Fuel Element after 1 a/o Burnup.

EI-5756

FIG. 131. Appearance of Type 304 Stainless Steel Container Capsule from ANL-55-9 UNC-ANL Paste Fuel Element Irradiation

130). The stainless steel jacket also appeared to be severely distorted and may have been breached in one area. The redistribution of the fuel in small clusters apparently resulted in high temperatures within the capsule since the control and measuring thermocouples were no longer at fuel locations. The existence of these high temperatures is illustrated by

the appearance of the Type 304 stainless steel container capsule, which was warped and oxidized along the length of the entire fuel element (Figure 131).

Postirradiation evaluation of the paste fuel element will continue after the fission-gas measurement in the capsule is completed.

3. Hydrogen in Irradiated Pressure-Vessel Steel (A. D. ROSSIN)

Catastrophic delayed failure due to hydrogen embrittlement has been observed in high-strength steels, but not in structural steels like 212-B. The strength level of the steel is one of the critical parameters controlling the susceptibility of steel to hydrogen-induced delayed failure. Since irradiation raises the strength level of pressure-vessel steel, concern has been expressed that irradiation-hardened 212-B could become susceptible to hydrogen embrittlement.

Hydrogen-induced, delayed, brittle failure results in sudden breaking of a high-strength steel at relatively low stresses, after a time period under sustained loads. For example, an ultra-high strength steel, such as quenched and tempered 4340 with a yield stress of 270,000 psi (190 kg/mm²), is charged with hydrogen and then loaded in a stress-rupture test. At a stress of 130,000 psi (91 kg/mm²) charged specimens fail catastrophically after one hour. In a normal tensile test very little difference can be observed between charged and uncharged specimens.

The purposes of this program were to measure the effect of hydrogen on a pressure-vessel steel, and to find out whether or not catastrophic, delayed brittle failure could occur in such low-strength materials. Then, irradiated and strengthened 212-B was charged and its delayed-failure behavior evaluated. Standard tensile tests of notched and unnotched specimens, and stress-rupture tests of notched specimens were performed at room temperature.

Two different hydrogen contents, obtained by electrolytic charging, were studied. The first, sufficient to cause catastrophic delayed failure in quenched and tempered 4340 at 20% of its notch tensile strength (NTS), is referred to as Charge A, and it had an

average hydrogen content of about 0.7 to 0.8 ppm hydrogen by weight. The second, called High Charge, employed much more severe charging conditions, and a hydrogen content about ten times as great was obtained.

The increase in the notch tensile strength of 212-B due to the irradiation in CP-5 is shown in Figure 132 and runs from 22 to 34%. The 20% difference in flux rate over the length of the capsule is enough to produce a spread of about 9% in notch tensile strength. Over this fairly short range the dependence of NTS versus neutron fluence is practically linear. This linearity makes it possible to correct all specimens to one level of exposure for analysis of the mechanical test data.

Failure of a notched specimen under constant load is known to occur at stresses somewhat below the notch tensile strength. This behavior is observed without the presence of hydrogen, but generally speaking the stress levels are almost as high as the notch tensile strength of the material. With hydrogen, the notch tensile strength is lowered by 4 or 5% for Charge A and 9% for the High Charge condition.

Stress-rupture tests were run on control and as-irradiated material to try to determine the lower critical stress as a function of the notch tensile strength. The lower critical stress is that stress below which no delayed failures are observed regardless of the length of time the specimen is loaded. Similar tests were conducted on specimens charged with hydrogen, both for Charge A and for the High Charge. The data are correlated by plotting the applied stress as a percent of the unhydrogenated notch tensile strength for each test, as in Figure 133.

In this chart a square indicates the notch tensile

strength of a hydrogenated specimen as a percent of the unhydrogenated NTS. Thus, under "Charge A Unirradiated" a square shows that the charged NTS was about 95% of the uncharged NTS. The time to failure, in hours, is indicated for each stress-rupture test in which failure occurred. An X is used, instead of a number, to indicate a test that did not fail in 100 hours. The lower critical stress (LCS) must be above all X's for a given condition.

A trend can be seen from these results. The narrow band where delayed failure is observed lies between the notch tensile strength and the lower critical stress. The band is broader for steels with higher strength level or heavier hydrogen charge. However, the delayed failure range of stresses seems to lie between about 90 and 95% of the charged NTS for the same charging condition. In no case is a catastrophic strength loss, so typical of hardened 4340, observed.

106-8826 Rev. 1

FIG. 132. 212-B Notch Tensile Strength vs Neutron Exposure. One RDU = 1 fission neutron.

106-8829

FIG. 133. Correlation of Tensile and Stress-Rupture Test Results for 212-B; Applied Stress as a Percent of Unhydrogenated NTS.

106-8830

FIG. 134. Delayed Failure of High Charge 212-B Compared with Results of Cain.⁽⁸⁷⁾

Irradiated specimens charged to Condition A show no particular effect attributable to hydrogen. It is evident that Charge A does not introduce enough hydrogen into 212-B to cause significant embrittlement.

The High Charge condition was selected because it caused a significant loss in mechanical properties of the 212-B. The amount of hydrogen charged is far more than that necessary to embrittle high-strength steels completely, and is twice the amount, in milliamperes per minute (charging current $\times$ time), as that which was used by Cain and Troiano⁽⁸⁷⁾ to embrittle normalized steel. The High Charge probably represents a saturation charge for the arrangement and temperature used.

The results are compared with Cain's in Figure 134. He studied a pearlitic 4620 steel for application in a hydrogen sulfide environment. Delayed failure was observed under High Charge conditions in about 0.2 hours. A lower critical stress of 100,000 psi, or about 68% NTS was found. This steel had a tensile strength of 100,000 psi and a notch tensile strength of 150,000 psi. This is almost the same as strength range of the irradiated 212-B tested. Despite the High Charge and the fact that the irradiated steel is brittle, it shows no sharp dropoff or great reduction in its lower critical stress. In fact, the LCS is about 80% of the NTS.

Thus, for this pearlitic steel 212-B the pattern of the delayed failure behavior shows a lower critical stress at about 90% of the charged NTS. This range is typical for uncharged specimens as well. However, the NTS itself is lowered by hydrogen. This behavior suggests that either the hydrogen does not diffuse as well

⁽⁸⁷⁾ Cain, W. M., and Troiano, A. R., *Steel Structure and Hydrogen Embrittlement*, Petroleum Engineer (May 1965).

in lower strength steel, or if it diffuses it does not build up critical concentrations.

Hydrogen embrittlement is a quantitative phenomenon. It requires a multiaxial elastic strain field for preferential diffusion and a temperature high enough to permit diffusion but low enough to keep the outgassing rate relatively slow. Failure occurs after an incubation period during which the critical concentration of hydrogen builds up by diffusion in the region of the most intense stress field.

In lower-strength steels, like 212-B, yielding occurs at stress levels below those necessary to produce the elastic strains needed for preferential diffusion. The intense strain field is never formed, so no critical con-

centration is built up. Highly charged specimens contain enough hydrogen to reduce the strength and ductility without much diffusion. Thus, the fear that pressure vessel steel, strengthened by neutron irradiation, could become susceptible, might be justified.

In general, steels used for reactor vessels have relatively low strength levels. But even more important, the conditions tend to limit the amount of hydrogen available, and the temperature of operation causes rapid outgassing. In view of these facts and the load range found necessary to cause failure in these experiments, the possibility of a catastrophic hydrogen-induced delayed, brittle failure in a 212-B reactor vessel need not be considered credible.

G. DEVELOPMENT OF CORROSION-RESISTANT JACKET AND STRUCTURAL MATERIALS

1. Mechanism-Related Studies Applied to Corrosion in Sodium

a. CORROSION MECHANISMS IN REFRACTORY-METAL/LIQUID-METAL SYSTEMS (T. F. KASSNER AND D. L. RINK)

The rotating-disc study of the dissolution kinetics of tantalum in liquid tin that was undertaken to test the applicability of the convective-diffusion model for mass transport in a high-temperature liquid metal system has been completed. A description of the apparatus and experimental methods was presented in the Annual Report for 1965 (ANL-7155) with some of the initial results.

The convective-diffusion model for mass transport to or away from a rotating-disc sample set forth by Levich⁸⁸ was extended in ANL-6985 to include the range of Schmidt numbers normally encountered in liquid metal systems at high temperatures. The maximum liquid-diffusion controlled mass flux from a disc sample undergoing dissolution in a large volume of liquid was expressed as

$$J_m = 0.554 I_{(D/\nu)}^{-1} D^{2/3} \nu^{-1/6} \omega^{1/2} (C_{\text{sat}} - C_B) \quad (1)$$

where,

D = diffusion coefficient of the solute in the liquid, cm²/sec.

ν = kinematic viscosity of the liquid, cm²/sec.

ω = angular velocity in the disc, radians/sec.

C_{sat} = equilibrium solubility of the solute in the liquid, gm/cm³.

C_B = initial solute concentration of the liquid at time = 0, gm/cm³.

$I_{(D/\nu)}$ = value of the integrate that is obtained from the solution to the convective-diffusion equation and is a function of the reciprocal Schmidt number. Values of $I_{(D/\nu)}$ are listed in Table 67 for a number of D/ν values.

Equation (1) is applicable to laminar flow, which for a polished and dynamically balanced disc extends to Reynolds numbers of the order of 10⁵. The Reynolds number for a disc of radius R is defined as $\text{Re} = \omega R^2/\nu$. For the 5.08 cm diameter discs used in this work, the upper limit for ω was ~ 20 radians/sec at the higher temperatures.

The temperature dependence of the diffusion-con-

trolled dissolution flux was obtained by inserting the following expressions for the temperature dependence of D , ν , and C_{sat} into Equation (1).

$$D = D_0 \exp\left(\frac{-Q_D}{RT}\right) \quad (2)$$

$$\nu = \nu_0 \exp\left(\frac{+Q_\nu}{RT}\right) \quad (3)$$

$$C_{\text{sat}} = C_0 \exp\left(\frac{-\Delta H_{\text{soln}}}{RT}\right) \quad (4)$$

The result is given below for the case where the initial solute concentration of the liquid, C_B , is zero:

$$J_m = 0.554 I_{(D/\nu)}^{-1} D_0^{2/3} \nu_0^{-1/6} \omega^{1/2} C_0 \exp\left(-\frac{4Q_D + Q_\nu + 6\Delta H_{\text{soln}}}{6RT}\right) \quad (5)$$

TABLE 67. VALUE OF THE INTEGRAL $I_{(D/\nu)}$ FOR A RANGE OF SCHMIDT NUMBERS BETWEEN 4 AND 1000

(Schmidt No.) ⁻¹	Integration Limit	Value of the Integral
(D/ν)	$1.9944 (\nu/D)^{1/3}$	$I_{(D/\nu)}$
0	∞	0.8934
0.001	19.944	0.9209
0.002	15.830	0.9286
0.003	13.828	0.9341
0.004	12.564	0.9305
0.005	11.663	0.9424
0.006	10.967	0.9457
0.007	10.426	0.9487
0.008	9.972	0.9515
0.009	9.588	0.9541
0.010	9.257	0.9564
0.020	7.347	0.9747
0.030	6.419	0.9877
0.040	5.832	0.9981
0.050	5.414	1.0068
0.060	5.094	1.0143
0.070	4.839	1.0209
0.080	4.629	1.0268
0.090	4.450	1.0321
0.100	4.297	1.0368
0.110	4.162	1.0412
0.120	4.043	1.0451
0.130	3.937	1.0488
0.140	3.841	1.0521
0.150	3.754	1.0552
0.160	3.674	1.0580
0.180	3.532	1.0631
0.200	3.410	1.0675
0.250	3.166	1.0762

⁽⁸⁸⁾ Levich, V. G., *Physiochemical Hydrodynamics*, pp. 60-72, Prentice-Hall, Inc., Englewood Cliffs, New Jersey, 1962 (2nd ed.).

106-9218

FIG. 135. Temperature Dependence of the Solubility of Tantalum in Liquid Tin.

From Equation (5), the temperature dependence of the maximum dissolution flux, Q_{J_m} , is related to the overall heat of solution of the solute in the liquid, ΔH_{soln} , and the activation energies for solute diffusion, Q_D , and viscosity, Q_v , by the relation:

$$Q_{J_m} = \frac{1}{6} (4Q_D + Q_v + 6\Delta H_{\text{soln}}) \quad (6)$$

Sufficient experimental data have been obtained to test Equation (1) for the magnitude of the dissolution flux (J_m) and Equation (6) for the temperature dependence of the flux (Q_{J_m}).

Results

The solubility of tantalum in liquid tin was determined from data obtained from the dissolution curves and also from a solubility run in which equilibration periods from 48 to 100 hours at each temperature were used. Each point in Figure 135 represents the average

of a number of determinations. The least squares equation for the data is given with 95% confidence limits.

The viscosity data for liquid tin in Figure 136 were obtained from the literature.⁽⁸⁹⁻⁹²⁾ The least squares line was fitted to Gebhardt's⁽⁸⁹⁾ data, which were measured over the largest temperature interval.

The results of measurements of the self-diffusion coefficient of liquid tin and tantalum in tin by the capillary-reservoir method are shown in Figure 137. The diffusivity of Sn-113 in liquid tin was determined

⁽⁸⁹⁾ Gebhardt, E., Becker, M., and Sebastian, H., *Z. Metallkunde*, **46**, 669-672 (1955).

⁽⁹⁰⁾ Sauerwald, F., and Töpler, K., *Zeitschrift für anorganische und allgemeine Chemie*, **157**, 117-137 (1926).

⁽⁹¹⁾ Rothwell, E., *Journal of the Institute of Metals*, **90**, 389-394 (1961-62).

⁽⁹²⁾ Culpin, M. F., *Physical Society of London Proceedings, Section B*, **70**, 1069-1077 (1957).

106-9219

Fig. 136. Temperature Dependence of the Viscosity of Liquid Tin.

to check out the diffusion cell and these data are in agreement with the data of Careri⁽⁹³⁾ and Ma⁽⁹⁴⁾ for temperatures below 800°C. The data for the diffusion coefficient of Ta-182 in liquid tin fall below the tin self-diffusion data. This is in agreement with the modified Cohen-Turnbull model⁽⁹⁵⁾ for solute self-diffusion in liquids; however, the activation energy of 4,265 cal/mole for tantalum diffusion from the model is not in good agreement with the experimental value of 1,925 cal/mole. Values of D_0 and Q_D from the least squares line for the experimental data were used in obtaining values for J_m and Q_{J_m} in Equations (5) and (6) respectively.

Figure 138 illustrates the temperature dependence of the dissolution flux at a rotational speed of 10.0 rpm. The dashed line gives the dissolution flux predicted by Equation (5) based upon the data in Figures 135 to 137. Figure 138 indicates that as the temperature increases, the dissolution flux approaches values predicted by the model.

The velocity dependence of the dissolution flux at four temperatures is shown on Figure 139. The straight line portions of the curves through the 1100 and 1200°C

data have a slope of 1/2 on the logarithmic plot. The half-power velocity dependence of the dissolution flux at constant temperature predicted by Equation (1) is observed at the higher temperatures over an appreciable velocity range.

All of the experimental dissolution data obtained in this study are plotted in Figure 140. The high-temperature portion of these curves for the velocities noted on the figure were calculated from Equation (5). The slope of the lines correspond to an activation energy, Q_{J_m} , of 16,870 cal/mole, Equation (6).

The data in Figure 140 provide an excellent example of how the temperature coefficient of a heterogeneous reaction can be used to distinguish between reaction types. If the activation energy for the surface reaction rate (i.e., the rate of transport of tantalum from the sample surface to the boundary layer) is greater than the total activation energy for diffusion control, Equation (6), a change in slope in the Arrhenius plot will result, indicating reaction control at the low temperatures. The above situation is analogous to limiting case I described by Riddiford.⁽⁹⁶⁾

When the observed dissolution rate is a function of both the rate of the surface reaction and the rate of transport through the liquid boundary layer, a change in the experimental conditions can result in a shift of control toward one or the other of these limiting cases. This is illustrated in Figure 140 by considering, for example, at 1100°C, a decrease in the velocity from 150 to 5 rpm. This decrease in velocity shifts the dissolution process from mixed-transport control to diffusion control. The effect of increasing temperature on the transition of the dissolution process from reaction control through mixed control, to diffusion control is best illustrated by the 10.0 rpm data in Figure 138. A more quantitative treatment of the temperature dependence of the dissolution rates in the mixed control region will be presented in the final report on this work.

Future work with the rotating disc technique will be directed toward the investigation of the considerably more complex reaction processes that occur in the alkali metal systems. An apparatus to conduct these studies has been designed and is being assembled.

b. CALCULATIONS TO DETERMINE THE DISTRIBUTION COEFFICIENT OF OXYGEN IN Ta-O-Na AND Nb-O-Na SYSTEMS AND THE KINETICS OF OXYGEN SOLUTION IN TANTALUM (T. F. KASSNER AND D. L. SMITH)

Corrosion mechanism studies in refractory metal sodium systems require a firm knowledge of the phas-

⁽⁹³⁾ Careri, G., Paloetti, A., and Vicentine, M., *Nuovo Cimento, Series X*, **10**, 1088-99 (1958).

⁽⁹⁴⁾ Ma, C. H., and Swalin, R. A., *J. Chem. Phys.* **36**, 3014-3018 (1962).

⁽⁹⁵⁾ Kassner, T. F., Russell, R. J., and Grace, R. E., *Transactions of the ASM*, **55**, 858-865 (1962).

⁽⁹⁶⁾ Riddiford, A. C., *Journal of Physical Chemistry*, **56**, 745-748 (1952).

106-9220

FIG. 137. Temperature Dependence of the Diffusion Coefficient of Sn-113 and Ta-182 in Liquid Tin.

equilibria as a function of both temperature and interstitial element concentrations. Calculations for the partitioning of oxygen in the tantalum-sodium and niobium-sodium systems have been made and were used to predict the kinetics of oxygen solution in tantalum for the limiting case in which oxygen transport processes in the liquid are not controlling, oxide film formation does not occur, and dissolution of the solid metal is not a significant factor (e.g. an isothermal closed system with a fixed low oxygen concentration in the sodium).

(1) Partitioning of Oxygen

The standard free energy of formation of the oxide phase in equilibrium with the oxygen saturated metal and the equilibrium solubility of oxygen are required as a function of temperature for each metal in order to calculate the distribution coefficients.

A survey of the literature was made to obtain free energy and solubility data for the systems of interest.

The data we believe to be most reliable for the solubility of oxygen in the three metals are shown in Figures 141, 142 and 143 with the equations obtained by the method of least squares. The low temperature data for solubility of oxygen in sodium are the results of a recent study⁽⁹⁷⁾ and are considerably lower than values previously reported. The standard free energies of formation for the oxides (calories per mole of oxygen) were obtained from Bureau of Mines Bulletin 542 for sodium oxide (Na_2O),

$$\Delta F_{\text{Na}_2\text{O}}^\circ = -100,120 + 34.60 T \quad (1)$$

and from Worrell's⁽⁹⁸⁾ data for tantalum oxide (Ta_2O_5) and niobium oxide (NbO),

$$\Delta F_{\text{Ta}_2\text{O}_5}^\circ = -96,320 + 19.44 T \quad (2)$$

$$\Delta F_{\text{NbO}}^\circ = -100,350 + 21.42 T \quad (3)$$

⁽⁹⁷⁾ Rutkauskas, V. J., USAEC Report LA-3524, 1966.

⁽⁹⁸⁾ Worrell, W. L., Proceedings of the Symposium on Thermodynamics, Vol. 1, pp. 131-143, IAEA, Vienna (1965).

106-9221

FIG. 138. Temperature Dependence of the Maximum Dissolution Flux of Tantalum into Liquid Tin at Constant Angular Velocity.

The distribution coefficient, which is the equilibrium activity ratio of oxygen in the refractory metal to oxygen in sodium, is derived by equating the partial molal free energy of oxygen in the two metals. It is assumed that the dilute solutions behave ideally ($a_o = N_o$). A complete development of the distribution coefficient will be included in an ANL report in press. The result obtained from the free energy and solubility data given previously for the tantalum-sodium system is expressed below in units of weight distribution of oxygen,

$$K_w = \frac{C_o \text{ in Ta}}{C_o \text{ in Na}} = 7.751 \exp \left[\frac{1098}{T} \right]; \quad \frac{\text{ppm } o \text{ in Ta}}{\text{ppm } o \text{ in Na}} \quad (4)$$

The similar relation for the niobium-sodium system is

$$K_u = \frac{C_o \text{ in Nb}}{C_o \text{ in Na}} = 7.733 \exp \left[\frac{2551}{T} \right]; \quad \frac{\text{ppm } o \text{ in Nb}}{\text{ppm } o \text{ in Na}} \quad (5)$$

Figure 144 is a plot of the calculated distribution coefficients, K_w , as a function of temperature for the two systems. Experimental values for the tantalum-sodium system have been reported by Raines et al.⁽⁹⁹⁾ Their values at 500 and 600°C ranged from 2 to 20 and 1 to 10, respectively, compared to calculated values of 32.1 and 25.5 obtained for the two temperatures from Equation 4.

The oxygen concentrations in sodium in equilibrium with the oxide phases Ta_2O_5 and NbO are obtained by substituting the oxygen solubility data for tantalum and niobium into Equations 4 and 5, respectively. The oxygen concentration in sodium necessary to produce a Ta_2O_5 film on tantalum is shown in Figure 145 as a function of temperature. Figure 146 shows a similar plot for the niobium-sodium system. The oxygen concentration in sodium required for the formation of the second oxide phase, NbO_2 , was also calculated from Worrell's⁽¹⁰³⁾ free energy data. Figure 146 indicates that solution of oxygen in tantalum occurs over the range of temperatures and oxygen levels in sodium normally of interest in reactor systems. The data in Figure 146 for niobium show that in addition to oxygen solution, film formation can also occur for equivalent oxygen levels in sodium depending upon the temperature.

(2) Kinetics of Oxygen Solution

If we may neglect transport problems in the liquid, dissolution of the solid metal, and only consider conditions in Figure 146 where film formation does not occur; the kinetics of oxygen solution in tantalum can be predicted as a function of oxygen concentration in the sodium, temperature, and initial oxygen concentration in the tantalum. The solution to Fick's second law for the case of diffusion into a semi-infinite slab in which the surface concentration remains constant with time can be written as:

$$\frac{C(x,t) - C_0}{C_s - C_0} = \text{erfc} \left[\frac{x}{2\sqrt{Dt}} \right] \quad (6)$$

where

$C(x,t)$ = concentration of oxygen in the sample
gm o/cm³, at position x , and time, t .

C_s = surface concentration of oxygen in the sample, gm o/cm³.

⁽⁹⁹⁾ Raines, G. E., Weaver, C. V., and Stang, J. H., BMI-1284 (1958).

106-9222

FIG. 139. Velocity Dependence of the Maximum Dissolution Flux of Tantalum into Liquid Tin.

C_0 = initial concentration of oxygen in the sample, gm o/cm³.

D = diffusion coefficient of oxygen in sample, cm²/sec.

The total quantity of oxygen, $M(t)$, diffusing into the slab in a time, t , can be obtained by inserting the differential form of Equation 6 into Fick's first law and integrating the resulting equation. The result is:

$$M(t) = 2A(C_s - C_0) (Dt/\pi)^{1/2} \quad (7)$$

The slope of a plot of $[M(t)/A]^2$ versus time yields the parabolic rate constant, K_p ,

$$K_p = (4D/\pi) (C_s - C_0)^2 \quad (8)$$

The parabolic rate constants for oxygen solution in tantalum and niobium have been calculated as a function of temperature for specific oxygen levels in sodium and initial oxygen concentrations in the refractory metals. Diffusion data for oxygen in the refractory metals have been compiled by Peterson⁽¹⁰⁰⁾ and the combined data of several authors for diffusion of oxy-

gen in tantalum are shown in Figure 147. The values of C_s in Equation 8 were obtained as a function of temperature from the partitioning relations (Equations 4 and 5) for fixed oxygen concentrations in sodium. It was necessary to convert the concentrations (ppm o by weight) to the proper units (gm o/cm³ Ta) for use in Equation 8. Figure 148 is a plot of $\log K_p$ versus reciprocal temperature for the case of zero initial oxygen in tantalum ($C_0 = 0$).

The activation energy for the parabolic rate constant in Figure 148 can be interpreted in terms of the temperature dependence of Equation 8 when C_0 is zero.

$$-R \frac{\partial \ln K_p}{\partial \left(\frac{1}{T}\right)} = -R \frac{\partial \ln D}{\partial \left(\frac{1}{T}\right)} - 2R \frac{\partial \ln C_s}{\partial \left(\frac{1}{T}\right)} \quad (9)$$

or

$$Q_{K_p} = Q_D - 2R \frac{\partial \ln K_w}{\partial \left(\frac{1}{T}\right)} \quad (10)$$

By inserting the value of the activation energy for

⁽¹⁰⁰⁾ Peterson, N. L., WADD-Technical Report-60-973 (1960).

106-9223

FIG. 140. The Temperature and Velocity Dependence of the Maximum Dissolution Flux of Tantalum into Liquid Tin under Laminar Flow Conditions.

diffusion from Figure 147 and the temperature dependence of K_w from Equation 4 into Equation 10, the activation energy for the solution process is 22,340 calories per mole.

Kofstad⁽¹⁰¹⁾ has shown that when tantalum is oxidized in low-pressure oxygen where the surface concentration remains near saturation, the second term on the right of equation 10 is the temperature dependence of the solubility of oxygen in tantalum. When we insert the value for $\partial \ln N/\partial(1/T)$ of -3434 from Figure 143 into Equation 10, the activation energy is calculated to be 40,350 calories per mole. This value is in agreement with Kofstad's experimental value of 35 to 40 kilocalories per mole for oxygen solution in tantalum at 0.01 torr oxygen pressure. These results indicate that the activation energy for oxygen solution in tantalum exposed to sodium (when $C_0 = 0$) is somewhat less than the activation energy for oxygen diffusion

⁽¹⁰¹⁾ Kofstad, P., J. Less-Common Metals, **7**, pp. 241-266 (1964).

in tantalum and about one-half of the activation energy for oxygen solution in tantalum exposed to low pressure oxygen. Figure 149 is a typical plot of $\log K_p$ versus reciprocal temperature obtained when the initial concentration of oxygen in tantalum, C_0 , assumes a reasonable value. At low oxygen levels in sodium, the activation energy, Q_{K_p} , is less than the value of 22,340 calories per mole obtained previously. Below 3 ppm oxygen in sodium, the rate constants in Figure 150 go through a maxima and then decrease with increasing temperature. The effect of initial oxygen concentration in the tantalum on K_p was determined at constant temperature from a number of plots similar to Figure 147. The results for several oxygen levels in sodium at 600°C are shown in Figure 150. This plot indicates that an accurate determination of the oxygen concentration in both tantalum and sodium is necessary when experiments are conducted in low oxygen sodium.

The remaining data for the tantalum-oxygen-sodium system and similar data for the niobium-oxygen-sodium system will be reported in an ANL report in preparation. Experimental data will be available in the near future to further verify the results of these calculations.

c. POLARIZATION STUDIES IN LIQUID-METAL ENVIRONMENT (C. A. YOUNGDAHL, J. C. TEZAK, AND S. GREENBERG)

Polarization studies in the oxygenated sodium environment at 540°C have been pursued to demonstrate effects of polarizing current on corrosion and to gain information relevant to the corrosion process. As has been indicated in previous reports, internal shorting of the test cell by essentially oxygen-free sodium condensate has made it difficult to obtain consistently reliable data. Efforts during the past year have met with only limited success and the program has been essentially suspended until suitable measuring techniques are developed. Possibilities include use of a metal (or alloy) displaying a much lower rate of oxygen absorption or lower oxygen solubility.

The more recent attempts at improvement of techniques as well as a summary of tentative conclusions are presented below. A topical report summarizing the program to date is in preparation.

Briefly, attempts to prevent condensate shorting have principally involved efforts to provide and maintain an insulating surface coating on electrode surfaces extending through the oxygenated sodium-sodium vapor interface in the cell. Introduction of BaO_2 vapor into the vapor space to provide oxygen for maintenance of an oxide film on the zirconium electrode shank (to compensate for oxygen absorbed from the film by underlying zirconium metal) did not produce the needed degree of insulation (a dark film was pro-

06-9224

FIG. 141. Temperature Dependence of the Solubility of Oxygen in Sodium.^(97, 102)

duced on the metal). Similar results were obtained when oxygen enrichment of underlying zirconium was attempted by (a) repeated anodizing (500 volts) and absorption cycles and (b) repeated oxidation and diffusion cycles (900°C). A zirconium sulfide film (readily produced on a zirconium electrode) displayed little tendency to diffuse into underlying metal during exposure to vacuum at 520°C but was not stable in sodium vapor. The best electrode performance was obtained by a grown surface oxide produced in a plasma torch flame. The oxide was subsequently coated with alumina in the torch apparatus. However, sufficient moisture was apparently incorporated into this coating to result in the surface spotting problem described in previous reports.

The general conclusions of the study as a whole may be summarized as follows:

- (a) Polarization studies are possible, though troublesome, in a high-temperature liquid-sodium system.
- (b) "Polarization" curves, i.e. cell terminal voltage

variations with time at constant imposed current may be obtained for zirconium samples in such a system. These curves are interpreted as primarily the results of resistance changes at the surface of the sample being corroded.

(c) The thickness of the corrosion film of such samples may be reduced by externally applied polarization current. Excessive data scatter precludes an unequivocal statement of this conclusion in spite of a significant quantity of evidence in support of it.

(d) Of a variety of sample metals tested none displayed a solution potential comparable to those commonly observed in aqueous media at lower temperatures. Corrosion films free of effective short-circuit paths between sodium and sample metal would appear to be formed only under conditions such as those specially maintained in this study (but not consistently even under such conditions). Low resistance of oxygen-deficient films may contribute to low cell voltage without precluding an effect on corrosion of imposed current. However, except for a number of zirconium specimens, the samples tested have been definitely

⁽¹⁰²⁾ Noden, J. D. and Bagley, K. Q., UKAEA Report RDB (C)-TN-80, 1954.

106-9225

FIG. 142. Temperature Dependence of the Solubility of Oxygen in Tantalum.⁽¹⁰³⁾

106-9226 Rev. 1

FIG. 143. Temperature Dependence of the Solubility of Oxygen in Niobium.⁽¹⁰⁴⁻¹⁰⁶⁾

106-9227

FIG. 144. Temperature Dependence of the Distribution Coefficient of Oxygen between Tantalum and Sodium and Niobium and Sodium.

short circuited to the sodium in the test cell. Under conditions much different from those of this program, the corrosion conditions that would obtain are apparently similar to those of an externally short-circuited cell, i.e., the anodic features of the corrosion reaction are of controlling importance.

As has been described, oxygen absorption by zirconium

has greatly affected the behavior of samples in this study. The importance of this process, which is extraneous to the electrochemical phenomenon, to corrosion at elevated temperatures is great, and not limited to zirconium. Successful application of electrochemical techniques to systems of general interest may depend on the employment of materials less subject to such extraneous processes.

Other results of interest arising from this study have included information pertaining to the unpolarized corrosion behavior of a variety of metals in highly oxygenated sodium, effects associated with sodium moisture content, information regarding glovebox atmosphere requirements, information with respect to the

⁽¹⁰³⁾ Gebhardt, V. E., and Seghezzi, H. D., *Z. Metallkunde*, **50**, 521-527 (1959).

⁽¹⁰⁴⁾ Gebhardt, V. E., and Rothenbouher, R., *Z. Metallkunde*, **54**, 623-630 (1963).

⁽¹⁰⁵⁾ Lenel, F. V., and Hulsizer, W. R., AROD-2530-2 (1963).

⁽¹⁰⁶⁾ Lenel, F. V., Regitz, L. J., and Hulsizer, W. R., AROD-2530-1 (1962).

106-9228

FIG. 145. Temperature Dependence of the Oxygen Concentration in Sodium in Equilibrium with Ta₂O₅ and Oxygen Saturated Tantalum.

106-9229

FIG. 146. Temperature Dependence of the Oxygen Concentration in Sodium for the Equilibria between NbO and Oxygen Saturated Niobium and the Equilibria between NbO and NbO₂.

106-9230

FIG. 147. Temperature Dependence of the Diffusion Coefficient of Oxygen in Tantalum.⁽¹⁰⁵⁾

106-9231

FIG. 148. Temperature Dependence of the Parabolic Rate Constant for Oxygen Solution in Tantalum with Zero Initial Oxygen Content.

106-9232

FIG. 149. Temperature Dependence of the Parabolic Rate Constant for Oxygen Solution in Tantalum with an Initial Oxygen Content of 0.050 a/o Oxygen.

106-9233

FIG. 150. Effect of Initial Oxygen Concentration in Tantalum on the Parabolic Rate Constant for Oxygen Solution at 600°C.

hazard of contacting Teflon and NaK, development of a freezing technique for drying argon cover gas, and a method of capacitance measurement across corrosion films in mercury-Woods metal solution. Observations

in film-stripping experiments by a liquid-metal reduction technique contributed to the initiation of a new program, "Corrosion Inhibition by Dissolved Getters in Liquid-Sodium Environment."

2. Internal-Friction Techniques for Analysis of Oxygen in Sodium

(D. L. SMITH AND R. H. LEE)

As discussed previously, the principles of thermodynamics and kinetics, when properly applied to the problems of liquid metal corrosion, are powerful tools for understanding processes and systems of interest. Basic to the use of these tools in alkali metal systems is an accurate knowledge of the partition functions for interstitial impurity elements between the liquid and solid metals.

In the course of determining these equilibrium data, it became apparent that our experimental method, based on internal friction measurements, was potentially an extremely sensitive technique for the reliable determination of interstitial impurity concentrations in sodium to very low (<1 wt. ppm) levels.

Although we are not primarily interested in developing analytical techniques, this method is promising enough to warrant its description and a discussion of results at this time.

This method of analysis involves the equilibration, with respect to the interstitial element, of refractory-metal wires in liquid sodium. The high sensitivity of

internal friction to low interstitial impurity concentrations in body-centered-cubic metals permits accurate determination of these impurities in several refractory metals. Since each interstitial element (O, N, C, and probably H) has a characteristic internal friction peak, it may be possible to analyze for all of these elements in one test.

Previous information has indicated that oxygen is probably the most significant impurity in sodium corrosion, so emphasis was initially placed on this element. Available thermodynamic data indicated that tantalum would be the most appropriate refractory metal to use for the determination of oxygen in sodium.

Internal-friction peaks have been obtained for oxygen, nitrogen, and carbon in 0.51 mm diameter by 18.0 cm gage length tantalum wires. An oscillating frequency of 0.27 cps produces friction peaks at 134°C for oxygen, 316°C for nitrogen, and ~326°C for carbon. The close proximity of the nitrogen and carbon peaks makes their analysis slightly more difficult than that for oxygen. Figure 151 is an internal-friction curve for

FIG. 151. Internal Friction Curve for "As Received" Tantalum Wire.

106-9235

Fig. 152. Internal Friction Curve for "Degassed" Tantalum Wire.

106-9236

Fig. 153. Oxygen Concentration by Vacuum Fusion Analysis vs Internal Friction Peak Height for Tantalum Wire

"as received" tantalum wire. The small peak at 316°C is due primarily to nitrogen. Any contribution to this peak by carbon can be determined by measuring the distortion of the experimental curve from a theoretical curve with a single relaxation process, since the experimental peak is due to the combined effects of the carbon and nitrogen, and in this case the nitrogen contribution is predominant. The curve in Figure 152 was obtained for a specimen that had been outgassed at high temperature under vacuum. The oxygen peak de-

creased considerably and the small peak is now caused primarily by carbon, which has a peak temperature of 326°C at the given frequency.

A linear relationship between internal-friction peak height and oxygen concentration exists until oxygen-oxygen interactions become significant. This condition is reached at a concentration of several hundred parts per million by weight of oxygen in tantalum. This linear relationship, obtained in the range where vacuum fusion analysis is reliable, is shown in Figure 153. The

oxygen concentration in tantalum as a function of the internal friction peak height may be expressed as

$$C_o \text{ (ppm)} = 10850 Q^{-1}$$

The high sensitivity of the internal friction measurement is illustrated by well defined peaks which have been obtained with peak heights as low as 0.159×10^{-3} (1.73 wt. ppm O in Ta).

The determination of oxygen in sodium depends upon the equilibrium partitioning of oxygen between the sodium and tantalum. This partitioning can be calculated theoretically from basic thermodynamic data. A partial development is given on page 153 of this report, and a complete derivation will be included in an ANL report in press. The distribution coefficient, which is the equilibrium ratio of oxygen in tantalum to oxygen

in sodium, calculated from the best available data is given as a function of temperature and in units of weight distribution of oxygen by

$$K_w = \frac{C_o \text{ in Ta}}{C_o \text{ in Na}} = 7.751 \exp \left[\frac{1098}{T} \right]; \quad \frac{\text{ppm o in Ta}}{\text{ppm o in Na}}$$

This corresponds to a concentration of 25.5 wt. ppm oxygen in tantalum per ppm oxygen in sodium at 650°C. Since, as previously illustrated, the oxygen in tantalum can be measured accurately at low concentrations, the method has potential for measuring oxygen in sodium at concentrations less than one part per million.

The distribution coefficient is independent of concentration as long as the solubility limit for oxygen in either metal is not reached. Experimental verification

Fig. 154. Internal Friction Peak (Oxygen) for Tantalum Wire before and after Exposure to 650°C Sodium.

of the partitioning can be achieved at higher oxygen concentrations where other methods of analysis for oxygen in sodium are believed reliable.

Limited experimental data have indicated significant changes in the internal friction peak heights of tantalum samples after exposure to sodium. A high-oxygen tantalum sample exposed to 650°C sodium cold trapped at 120°C indicated a change in oxygen peak from 10.09×10^{-3} to 0.246×10^{-3} . An outgassed tantalum wire exposed to 650°C sodium cold trapped at 167°C showed an increase of the oxygen peak from $\sim 0.16 \times 10^{-3}$ to 4.11×10^{-3} .

Figure 154 illustrates the increase of the oxygen peak for the latter case. The cold trap temperature indicates a solubility of oxygen in sodium of 3.70 wt. ppm. However, a value of 13.3 wt. ppm oxygen in the sodium was obtained by mercury amalgamation analysis. Based on the theoretical distribution coefficient the internal friction peak gives an oxygen concentration in the sodium of 1.73 wt. ppm. If the cold trap solubility data is assumed to be the correct oxygen concentration, an experimental distribution coefficient of 12.0 is obtained. This value compares favorably with the other experimental data given previously. The mercury amalgamation method is believed to give high oxygen results since it does not distinguish between oxygen and other interstitial elements which form sodium compounds insoluble in mercury. This possibility has been verified by the analysis of sodium samples taken simultaneously from another sodium system. The mercury amalgamation method indicated a value of 9.3 wt. ppm oxygen in the sodium compared to a value of 1.37 wt.

ppm obtained by vacuum distillation analysis. The equipment for vacuum distillation analysis was not available on the sodium systems which were used for the previous tests.

An additional observation has resulted from the internal friction measurements on the tantalum wires exposed to sodium. In each case a considerable increase of the nitrogen peak has been detected. The relatively long time required for equilibration of nitrogen between sodium and tantalum has limited the accuracy of the nitrogen measurements. However, the peak heights obtained indicate several hundred parts per million nitrogen in tantalum in some cases. The significant lack of good thermodynamic data, particularly the solubility of nitrogen in sodium, has thus far prevented relating the concentration of nitrogen in tantalum to the nitrogen concentration in sodium. Although the nitrogen system has not been completely evaluated, the pickup of nitrogen by the tantalum emphasizes one of the advantages of this method; each interstitial element can be distinguished by its characteristic peak.

The nitrogen detection has resulted in an expanded investigation to determine whether a different refractory metal would be more appropriate as a compromise detector for all of the interstitial elements. The principal disadvantage of tantalum is the long equilibration time for nitrogen and carbon. An alternate solution of smaller diameter wire is also being investigated. The significant lack of good thermodynamic data has been a primary problem in determining interstitial elements other than oxygen.

3. Lithium-Corrosion Studies at Elevated Temperatures

(J. Y. N. WANG, W. D. McFALL, AND J. W. SCHLAMER)

a. INTRODUCTION

During the past year our efforts have been devoted to the study of corrosion inhibition in lithium systems at 1200°C. Work at higher temperatures (to 2500°C) has been postponed because of failure of the high-temperature furnace to operate properly.

There have been relatively few studies of corrosion inhibition in liquid metal systems. The early work of Nerad et al.⁽¹⁰⁷⁾ has shown that titanium dissolved in mercury resulted in the coating of steel samples with deposits of an intermetallic compound, thought to be Fe₂Ti. The coating prevented the iron from dissolving

in the mercury. Later, Weeks et al.⁽¹⁰⁸⁾ and Horsley et al.⁽¹⁰⁹⁾ showed that solution of zirconium leading to the formation of ZrN and ZrC films on steel surfaces are responsible for reducing the corrosion rate of steel in bismuth. Our recent work⁽¹¹⁰⁾ showed that the corrosion of titanium in mercury can be inhibited by dissolving nickel in the mercury. A protective surface layer—an intermetallic compound TiNi—was formed.

⁽¹⁰⁸⁾ Weeks, J. R., and Klamut, C. J., Reactions Between Steel Surfaces and Zirconium in Liquid Bismuth, *Nuc. Sci. and Eng.*, **8**, No. 2, 133-140 (1960).

⁽¹⁰⁹⁾ Horsley, G. W., and Maskrey, J. T., The Corrosion of 2½ Cr-1 Mo Steel by Liquid Bismuth, *J. Iron and Steel Inst.*, **189**, 139-148 (1958).

⁽¹¹⁰⁾ Wang, J. Y. N., Effect of Metallic Additives in Mercury Corrosion of Titanium, *Corrosion*, **21**(2), 57-61 (1965).

⁽¹⁰⁷⁾ Epstein, L. F., Compilation and Discussion of Unpublished Data of A. J. Nerad and his Associates at General Electric Co., *Liquid Metals Handbook*, 2nd Ed., 167-168 (1954).

Little is known about corrosion inhibition in alkali metals.

b. INFLUENCE OF SILICON ON THE LITHIUM CORROSION OF TANTALUM AT 1200°C

Tantalum is a potentially attractive reactor material for high-temperature service because of good mechanical properties and ease of fabrication, but previous work (Annual Report for 1965, p. 143 in ANL-7155) has shown that corrosion behavior in lithium is unacceptable above 1000°C. Refractory metal compounds with silicon such as $\text{TaSi}_2^{(111)}$ and $\text{MoSi}_2^{(112)}$ are, however, effective oxidation barriers, and silicon is soluble in liquid lithium. The performance of silicon as an inhibitor of the corrosion of tantalum in lithium therefore merited investigation.

Intergranular attack was completely prevented during a seven-day exposure of tantalum at 1200°C by 1.6 a/o Si dissolved in the lithium as shown in Figure 155. Tantalum exposed to silicon-containing lithium develops a hardened surface layer, attributed to the presence of silicon (demonstrated by chemical and spectrochemical analyses to be present). Results of microhardness traverses are in Figure 156. The surface layer, approximately 178 microns thick, contains silicon in the range of 30 to 340 ppm. No silicon has been detected on the surface of samples exposed in uninhibited lithium.

Microprobe study of the surface reaction layer (approximately 4μ thick) indicated an average composition of 73 w/o Ta and 10 w/o Si (absorption correction only—no corrections for fluorescence or atomic number). Figure 157a is the electron image of an exposed tantalum sample. Figures 157b and 157c are the Si K_α and Ta L_α X-ray images respectively (different areas were used for the electron and X-ray images). Figure 158 shows the relative concentrations of silicon and tantalum through the surface layer.

X-ray diffraction analysis of the surface reactor layer resulted in lattice constants closely corresponding to Ta_2Si (7.2 w/o Si). It is tentatively concluded that the observed inhibition is due to the formation of Ta_2Si on the surface of the tantalum.

c. THE INFLUENCE OF OTHER ADDITIONS ON THE LITHIUM CORROSION OF TANTALUM AT 1200°C

Yttrium and titanium are deoxidizing agents for lithium and have been studied in an exploratory manner for effectiveness of inhibition. The use of yttrium re-

⁽¹¹¹⁾ Hallowell, J. B., Maykuth, D. J., and Ogden, H. R., *Coating for Tantalum-Base Alloys*, ASD-TDR-63-232, Feb. 1963.

⁽¹¹²⁾ Watchtell, R. C., and Seelig, R. P., *Diffusion Coating of Nonferrous Metals*, U.S. Patent 3,037,083, June 1962.

FIG. 155. Comparison of the Results of Silicon Inhibition on the Lithium Attack of Tantalum at 1200°C for Seven Days.

sulted in moderate acceleration of corrosion at 1200°C. No surface layers were observed. The use of titanium resulted in reduction of lithium nitrogen content from 50 to 15 ppm after seven days at 1200°C and no significant change in the molybdenum test capsule. (This was a preliminary test of the system. Exposures of tantalum are scheduled for subsequent tests.)

Exposure of tantalum to the Li-Na eutectic (3.4 a/o Na)⁽¹¹³⁾ at 1200°C resulted in much more severe corrosion than in pure lithium in the liquid phase. There was essentially no attack in the vapor phase (sodium rich).

⁽¹¹³⁾ Elliot, R. P., *Constitution of Primary Alloys*, First Supplement, B. 583, McGraw-Hill, New York, 1965.

106-9238

FIG. 156. Microhardness Profile of Tantalum Specimens Following Exposure to Lithium for Seven Days at 1200°C.

FIG. 157. Electron and X-ray Images Obtained in Microprobe Analysis of a Surface Layer on Tantalum Developed in Seven Days in Silicon-containing Lithium at 1200°C. (a) Electron Image; (b) SiK_α X-ray Image, and (c) TaL_α X-ray Image.

106-9239

FIG. 158. Microprobe Scan Lines (Penrecording) of X-ray Intensity vs Distance Indicating Relative Concentrations of Silicon and Tantalum of Various Depths of Surface Layer.

H. DEVELOPMENT OF TECHNIQUES OF FABRICATION AND TESTING

1. Fabrication of Tungsten and Tungsten-Alloy Tubing

(R. M. MAYFIELD AND W. R. BURT, JR.)

a. PURPOSE AND SCOPE OF PROGRAM

The purpose of this program is to devise and develop practical techniques for the fabrication of high-quality tungsten and tungsten-alloy tubing for high-temperature applications. Program results obtained before December 31, 1965 have been documented^(114,115) and will not be treated in detail, but mention of the work will be made where necessary to provide clarity and continuity.

While initial efforts centered on pure tungsten, program requirements and fabrication difficulties associated with the crack-propagation characteristics later led to dropping tungsten in favor of the W-25w/oRe alloy. Some limited work on the W-30w/oRe-30w/oMo alloy has also continued at ANL, complementing the more extensive effort being devoted to this alloy by GE-NMPO (Cincinnati).

Most all of the fabrication operations associated with these alloys have entailed difficulties such as surface striations resulting from the extrusion operation, lubrication problems, swage-point failures, tooling inadequacies, and many others. Some of these difficulties have received attention during the past year; some remain to be resolved.

b. PRIMARY FABRICATION

(1) Extrusion

In review, primary fabrication incorporates single or double extrusion of a commercially procured pressed and sintered sleeve with a modified version of the "filled-billet" technique developed by Nuclear Metals.⁽¹¹⁶⁾ The sleeve nominally 1.25 in. OD $\times$ 1.00 in. ID $\times$ 4 to 5 in. long is placed in a molybdenum can

with a molybdenum core and is extruded at approximately 1400°C at reduction ratios of more than about 4:1. If re-extrusion is to be employed (an expeditious method of reaching the final tube size), the composite product from a 4:1 primary extrusion is re-extruded at 1400°C and generally a 7:1 reduction ratio; yielding a tube measuring about 0.250 in. OD $\times$ 0.025 in. wall.

While this procedure has consistently produced sound tube-blanks suitable for secondary fabrication, much room for improvement exists. The process is tremendously expensive and the surface striations inherent with even a pressed and sintered fine-grained starting product have plagued subsequent fabrication. If an arc-cast starting product is favored (because of improvements in certain properties or because of improved economies due to simplified reclamation methods) even more problems may be expected with surface striations. The grain size of an arc-cast product would tend to be larger than a pressed and sintered product and surface quality would deteriorate in direct proportion to the increase in grain size.

The extruded surface finish problem can be corrected after core removal by a complete conditioning of both the inner and outer surfaces before further processing. This is an expensive and time-consuming process. The striations can also be minimized, to varying degrees, in subsequent processing operations as discussed in the following section.

Most all core-removal methods involve acid dissolution and the longer the length and smaller the diameter the more difficult the job. One of the better methods, confirmed at ANL under actual practice, is the GE-NMPO technique of using a small hafnium center core rod in the initial extrusion.⁽¹¹⁷⁾ A dilute hydrofluoric acid solution is directed continuously, against the center core until a clear passage is obtained, after which an appropriate acid solution can remove the balance of the molybdenum core material. This method can reduce the core removal time from days to hours, but it is not an inexpensive method. The removal of Nb-5w/oZr (D-14) cores by hydriding has been singularly unsuccessful.⁽¹¹⁸⁾

⁽¹¹⁴⁾ Burt, W. R., Jr., Katiyar, H. C., and Mayfield, R. M., *Development of Techniques for Fabrication of Small-Diameter Thin-Wall Tungsten Tubing*, Interim Progress Report covering the period from July 1, 1963 through December 31, 1963, ANL-6806.

⁽¹¹⁵⁾ Burt, W. R., Jr., Brillhart, D. C., and Mayfield, R. M., *Development of Techniques for Fabrication of Small-Diameter Thin-Wall Tungsten and Tungsten Alloy Tubing*, Interim Progress Report covering the period from January 1, 1964 through December 31, 1965, ANL-7151.

⁽¹¹⁶⁾ Isserow, Saul, et al., *Fabrication of Tungsten and Tungsten-25% Re Tubing*, Nuclear Metals Division of Textron, Incorporated, Nuclear Applications, Vol. 2, No. 4, pp. 304-307 (August 1966).

⁽¹¹⁷⁾ *High-Temperature Materials Program Progress Report No. 59, Part A*, GEMP-59A, p. 67 (May 31, 1966).

⁽¹¹⁸⁾ *Annual Progress Report for 1965, Metallurgy Division*, ANL-7155, p. 152.

(2) Tube-Reducing

The continued application of the extrusion technique to billets that are either "filled" or canned for mandrel use⁽¹¹⁹⁾ will require that alternate means for economic conditioning be considered. One such method is by tube-reduction and the ANL three roll tube-reducer⁽¹²⁰⁾ is being modified for warm working operations.

A marked improvement in both inner and outer surfaces of some extruded, annealed and mildly striated W-Re-Mo alloy tube-blanks has been demonstrated by tube-reduction at ANL. This work was interrupted by a roll design change but it will continue and, it is hoped, be extended to tungsten and tungsten-rhenium alloys, both of which are more difficult to fabricate than the ternary alloy.

A word of caution in this regard—the only salvation for grossly striated tube-blanks is extensive surface conditioning by machining or grinding. To tube-reduce a heavily striated product would be folly since the striations might be folded over or lapped causing serious problems in subsequent processing operations.

(3) Primary Fabrication of Tubing by Alternate Techniques

The 3M (Minnesota Mining and Manufacturing Company) process for producing tubing by powder extrusion and sintering⁽¹²¹⁾ merits further evaluation. This process could, within certain size limitations, replace extrusion as a primary tubing fabrication operation in processing tungsten and tungsten alloys. (Secondary fabrication efforts carried out at ANL on this type of material are described in a later section.)

The 3M method for producing tubing and the commercial processes used for sleeve production can produce comparable products with regard to density and grain size, but the 3M process yields internal and external surfaces that require little, if any, subsequent conditioning.

c. SECONDARY FABRICATION

(1) Ductile-Core Drawing Versus Plug Drawing

Secondary fabrication has followed two routes at ANL, ductile core and plug drawing. The former

⁽¹¹⁹⁾ Blakenship, C. P., and Gyorgak, C. A., *Extrusion of 1/2- and 3/8-Inch Diameter Thin-Wall Tungsten Tubing Using the Floating Mandrel Technique*, NASA-TN-D-3772, Lewis Research Center, Cleveland, Ohio (December 1966).

⁽¹²⁰⁾ Kramer, W. C., Burt, W. R., Jr., Karasek, F. J., Flinn, J. E., and Mayfield, R. M., *Vandium Alloy Screening Studies and Fabrication of V-15w/oTi-7.5w/oCr Tubing for Nuclear Fuel Cladding*, ANL-7206, p. 37 (August 1966).

⁽¹²¹⁾ Sowman, H. G., et al., *Fabrication of Tungsten Alloy Tubing*, COO-1518-4, Minnesota Mining and Manufacturing Company, St. Paul, Minnesota (December 23, 1966).

method utilizes the molybdenum core retained in the tube after extrusion; the core being removed at the final tube size by acid dissolution. As mentioned earlier in Section b(1) Extrusion, this is an unattractive and time-consuming process. The internal extrusion striations are not removed in ductile-core drawing since the molybdenum core is softer than the tungsten-alloy and provides no ironing effect to smooth the internal surface. The plug drawing process is performed on the tubing after core removal; generally with lighter reductions. Theoretically, the inner surface should be improved by this process and maximum dimensional control provided without the complication of mandrel or core removal. While plug drawing appears enticing it is at best a difficult operation and not practiced on a broad basis by many tube-fabricating specialists.

(2) Swage Pointing

Improved swage-pointing operations at ANL have minimized, if not eliminated point breakage and crack propagation. Higher pull forces with greater stress in the tip cross section can now be tolerated without premature failure in the W-Re and W-Re-Mo alloys.

Point failure invariably results if improper dies, inadequate heating methods or poor operator techniques are employed. While optimum swaging parameters have not been established, considerable progress has been made. RF (radio frequency inductive heating) is now employed under an inert atmosphere. Conventional cold-swaging dies having an 8° entry angle, 6 to 8% ovality and a moderately long blade length (2× diameter) have proved most successful over a range of temperatures. The tubing is swaged-pointed over molybdenum or other ductile-core materials.

Low entry-angle dies with large ovality (12%) should probably be avoided because they lead to cracking much sooner than with low ovality (6%) dies. Under any condition, if high-performance points are to be swaged the operation must be done with care. Frequent workpiece reheats may have to be combined with reasonable feed rates.

(3) Draw Lubricants

A wide variety of drawing lubricants have been evaluated during the reporting period. An alcohol suspension of WS₂ (1 to 2% solids) produces a better drawn surface than that obtained with the previously used mixture of graphite and powdered sugar in water. The WS₂ mixture has been used on the W-Re alloy for short exposures at 700°C with no evidence of surface contamination. A very thin film of this lubricant has significantly reduced the draw friction causing a marked lowering of the draw force required for a given reduction.

46186

150×

As-Drawn—47% R of A
Hardness: 52 R_c

46187

150×

Annealed: 1525°C—One Hour
Hardness: 44 R_c

FIG. 159. As-drawn (47% Reduction of Area) and Recrystallized Structure of W-25w/oRe Alloy Tubing.

(4) Ductile-Core Drawing

Significant improvements have been made in ductile-core drawing owing largely to gains made in the swage-pointing and lubrication areas.

Initial schedules called for ductile-core drawing W-Re alloys at 625° to 725°C with recrystallization anneals after two passes, each of 10% reduction in area. Heavier reductions are now possible in all tube sizes.

The microstructure of a tube section drawn over a ductile core to a 47% reduction of area at approximately 700°C and annealed at 1525°C for one hour is shown in Figure 159. The annealed hardness of the tubing before reduction was 45 R_c ; after reduction 52 R_c and after annealing at 1525°C for one hour 44 R_c .

Area reductions in excess of 60% have been successfully accomplished on smaller diameter (<0.140 in.) tubing. Precise heavy reduction drawing parameters and schedules have not been firmly established and on occasions some tube-cracking can be expected. Work will continue in this area since the economics of processing could be immensely improved by eliminating needless drawing and annealing operations.

(5) Plug Drawing

Plug drawing has been successfully accomplished on a W-Re tube size as small as 0.080 in. OD $\times$ 0.066 in. ID. Plugs are fabricated from T-1 class high speed steel and hardened to about 60 R_c . Drawing is performed at 650°C, the maximum temperature that the plug will normally withstand.

Plug drawn tubes are reduced about 10% (R of A) per pass with anneals after one or possibly two passes. Further work is expected to indicate—as for ductile-core drawn material—that greater reductions and/or lower drawing temperatures are possible.

d. Fabricability Evaluation of 3M-Produced Tubing

The fabricability of several small-diameter tubes (approximately 0.130 in. OD $\times$ 0.080 in. ID) of W-26a/oW and W-30a/oRe-30a/oMo alloys, fabricated at 3M by a powder extrusion technique, have been evaluated at ANL by both ductile-core and plug drawing operations. No surface conditioning of any type was required prior to drawing.

The results reported by 3M⁽¹²¹⁾ indicate that tubing of both alloys could be drawn in much the same manner as ANL extruded starting material. A 50% reduction of area could be accomplished on the W-Re alloy over a molybdenum core at 600°C. Similar drawing operations at room temperature were unsuccessful on the W-Re alloy but the W-Re-Mo alloy was reduced 35% and up to 68% at temperatures ranging from 300°C to 600°C without tube failure.

The inner diameter surfaces of the wrought 3M tubing were quite smooth—even after heavy reductions over a ductile core. This advantage in tube quality is gained through a lack of extrusion striations in the starting material. Metallography shows that many of the discrete voids present in the (approximately 95% dense) as-sintered starting material were closed up after a relatively heavy reduction by drawing. It seems reasonable to assume that suitable working of this material would produce final densities similar to those obtained by extrusion and drawing of pressed and sintered sleeves. Only cast materials would be expected to yield higher final density values.

e. FUTURE COURSE OF WORK

Future efforts will be directed toward process cost reductions without compromising final tube quality.

Simple means of conditioning the as-extruded surface of tube-blanks will be sought. Tube-reduction techniques will be employed to the maximum extent possible. Single-extruded tube-blanks (approximately 0.500 in. OD $\times$ 0.050 in. wall) will be processed to a range of intermediate tube sizes by a combination of ductile core, mandrel and/or plug drawing operations. Early core removal will be favored and subsequent operations will be minimized—utilizing maximum tolerable reductions with a minimum of in-process anneals. The major effort is being directed to the production of

improved ID surfaces by all feasible means. Tooling inadequacies are to be corrected and the use of ductile cores will be minimized. Arrangements are being made to provide RF (inductive) heating on the draw bench. This will remove the product length restriction now imposed by the resistance heating furnace.

Additional fabricability studies will be conducted on 3M-produced tubing as it becomes available. Larger tube sizes are desired so that more reduction can be accomplished before a limiting size of about 0.080 in. diameter is reached. This material, properly evaluated, could eventually eliminate the necessity and expense of extrusion operations as an operational prerequisite to subsequent processing.

2. Dimensional and Microstructural Changes During Tube Sinking (J. E. FLINN)

a. EXPERIMENTAL AND THEORETICAL STATUS

The need for a better understanding of the multi-axial stress-strain behavior of metals becomes evident when one attempts to analyze the plastic flow characteristics of tube bursting, fuel element and jacket swelling and metal forming. For these systems, it is difficult to separate into distinct components and isolate the various parameters contributing to a multi-axial stress-strain analysis. A current endeavor on elucidation of a mode of metal forming, tube sinking or hollow drawing, should aid in bridging the gap between the multi-axial and uniaxial deformation behavior of metals insofar as understanding is concerned.

Past considerations of tube sinking consisted of theo-

retical and experimental treatments that were incomplete. The experimental observations were so meager as to prevent theoretical treatments from properly predicting the stress-strain behavior, except possibly for thin-wall tubing. Two important parameters have received little attention either experimentally or theoretically. These are: (a) the stress-strain distribution across the tube wall before and after reduction; and (b) the initial thickness-to-radius ratio $t_0/r_0 = \gamma_0$ of the tube. For the latter parameter, tubes with γ_0 ratios of $0 \leq \gamma_0 \leq 1$ should be examined. The objectives of the tube-sinking study are:

1. Attempt to define the multi-axial stress-strain behavior. This includes both a macro and micro stress-strain analysis.
2. Attempt to distinguish between the mechanics of the tube-sinking process from the material properties.
3. Extend the analysis to any system that is subjected to multi-axial deformation.

b. DIMENSIONAL AND MICROSTRUCTURAL CHANGES

The sinking behavior of six metals of commercial purity were investigated. Each material, as shown in Table 68, possessed several γ_0 values and, in some instances, different outer diameters. Each tube was given a full anneal and then drawn through conical-shaped dies, with semi-die angles of 6° and 8°. Teflon was used for lubrication. After reduction the dimensional changes were recorded, and for some materials portions of tube were metallographically examined.

The observed strain behavior for mild steel and 1100S aluminum tubing is shown in Figures 160 to 163 which

TABLE 68. MATERIALS AND THEIR INITIAL GEOMETRICAL DIMENSIONS FOR STRAIN AND MICROSTRUCTURAL ANALYSIS

Material	Outer Diameter, D_o (in.)	$\gamma_0 = t_0/r_0$ Ratios
Aluminum (1100S)	$\frac{1}{2}$	0.844, 0.688, 0.564, 0.500, 0.376, 0.250, 0.130
α -Brass	$\frac{1}{2}$	0.500, 0.262, 0.128
α -Brass	1	0.258, 0.132, 0.066
Nickel	$\frac{1}{2}$	0.844, 0.680, 0.564, 0.500, 0.367, 0.250
Monel	$\frac{3}{4}$	0.316, 0.176
Mild Steel	$\frac{3}{4}$	0.324, 0.160
Mild Steel	$\frac{1}{2}$	0.454, 0.260, 0.144
Mild Steel	$\frac{3}{8}$	0.328
304 SS	1	0.468, 0.258, 0.135, 0.068, 0.037
304 SS	$\frac{1}{2}$	0.820, 0.692, 0.560, 0.500, 0.420, 0.372, 0.272, 0.250, 0.136

FIG. 160. Elongation Strain, ϵ_λ , vs $d_1/2\bar{r}_1$ for Mild Steel Tubing. $D_o = 1.27$ cm (0.50 in.).

FIG. 162. Elongation Strain, ϵ_λ , vs $d_1/2\bar{r}_1$ for Aluminum (1100S) Tubing. $D_o = 1.27$ cm (0.50 in.).

FIG. 161. Hoop Strain, ϵ_θ , vs $d_1/2\bar{r}_1$ for Mild Steel Tubing. $D_o = 1.27$ cm (0.50 in.).

FIG. 163. Hoop Strain, ϵ_θ , vs $d_1/2\bar{r}_1$ for Aluminum (1100S) Tubing. $D_o = 1.27$ cm (0.50 in.).

FIG 164. Thickness Strain vs Reduction for Aluminum (1100S) Tubing. $D_o = 1.27$ cm (0.50 in.).

exemplifies the strain results observed for the other tubing materials listed in Table 68. The limits for $d_j/2\bar{r}_j = 0$ and 1 in Figures 160 to 163 arise from expected strain changes for rod and thin-wall tubes ($t \rightarrow 0$), respectively, when constancy of volume considerations are incorporated into both limiting uses. The symbols in these four figures are defined as follows:*

$\epsilon_\lambda = \ln(l_j/l_0)$ —the true elongation strain, where l represents the length of the tube.

$\epsilon_\theta = \ln(\bar{r}_0/\bar{r}_j)$ —the true hoop strain, the bar representing the mean tube radii.

d_j = the inner diameter of the tube,

t_j = the tube wall thickness, and

$R = r_j/r_0$, ratio of the outer radius of the tube after j reduction passes to that before reduction.

For a given reduction, the strain curves for all materials appear to have the same general shape. How-

ever, the individual curves for equivalent reductions are not necessarily coincident.

From Figures 161 and 163 we see that there is an apparent tubing range of γ_0 's < 1 , where the change in the outer surface dimensions approach or are nearly equivalent to that for a rod. Also, the ϵ_λ curves possess an inflection point, which occurs near the same $d_j/2\bar{r}_j$ value for the observed maximum hoop strain, ϵ_θ (Figures 162 and 164).

For a given reduction and the assumption that the metal volume of the tube does not change, the difference between the ϵ_λ and ϵ_θ curves for the same $d_j/2\bar{r}_j$ value represents the thickness strain, $\ln(t_0/t_j)$. The arithmetic sign of this term is positive for wall thinning ($\epsilon_\lambda > \epsilon_\theta$) and negatives for thickening ($\epsilon_\lambda < \epsilon_\theta$). The wall thins when the elongation strain is predominant and the wall thickens when the hoop strain is predominant. The changes in wall thickness after reduction are more clearly visualized in Figures 164 and 165 for two materials.

* The subscript j , where $j = 0, 1, 2, 3 \dots$ represent the initial (0) and final (1, 2, 3 $\dots$) reduction sequence, respectively.

Fig. 165. Thickness Strain vs Reduction for α -Brass Tubing. $D_o = 1.27$ cm (0.50 in.).

Fig. 166. Micro-hardness Profiles at Various Reductions for 304 SS Tubing. $D_o = 2.54$ cm (1.00 in.) and $\gamma_0 = 0.468$.

Fig. 167. Micro-hardness Profiles at Various Reductions for 304 SS Tubing. $D_o = 2.54$ cm (1.00 in.) and $\gamma_0 = 0.258$.

FIG. 168. Micro-hardness Profiles at Various Reductions for 304 SS Tubing. $D_o = 2.54$ cm (1.00 in.) and $\gamma_0 = 0.068$.

FIG. 169. Grain Shape Profiles of Monel Tubing. $D_o = 1.91$ cm (0.75 in.) and $\gamma_0 = 0.316$.

Fig. 170. Grain Structure Across the Wall of Monel Tubing for Reductions, $R_{10} = 0.50$, $D_o = 0.75$ inch, and $\gamma_o = 0.316$.

The microstructural evaluation of the tube sinking study consists of metallography, grain boundary anisotropy and microhardness measurements. The observed microstructural changes are dependent upon the reduction and the γ_0 value of the tube. Radial microhardness profiles appear to reflect the work-hardening nature of the tube with reduction. The measurements of grain-boundary anisotropy represents the grain-shape profile. This latter portion of the study appears to be most promising for evaluating the stress-strain distribution across the tube wall.

Although both facets of the microstructural portion of the study have not been completed, the preliminary results are most interesting. Some hardness profiles observed for Type 304 ss tubing with various γ_0 values

are shown in Figures 166 to 168. It is apparent the profiles depend upon reduction and the γ_0 value.

The grain-shape profiles across the wall were determined from a lineal intercept analysis.⁽¹²²⁾ This type of analysis relates the grain shape to an ellipse for a two dimensional examination. The grain shapes for the transverse plane of Monel tubing are shown in Figure 169. The two reductions shown are $R_5 = 0.74$ and $R_{10} = 0.50$. The microstructure for the latter reduction is shown in Figure 170. A consideration of the individual grains as differential volume elements indicates the likelihood that the grain-shape analysis will aid in determining the stress-strain distribution.

⁽¹²²⁾ Philofsky, E. M., *Specification and Measurement of Lineal and Boundary Anisotropy*, M. S. Thesis, Northwestern University, Evanston, Ill. (1966).

3. Nondestructive Testing

a. DETERMINATION OF ELASTIC MODULI OF HIGH-TEMPERATURE MATERIALS BY ULTRASONICS (R. G. PETERSON)

The object of this program is to measure the temperature dependence of the elastic moduli of materials showing promise in high-temperature reactor applications. In this work pulsed ultrasonic waves are propagated along the length of test rod samples mounted in a vacuum furnace, and the transit times of pulses passing a heated, indexed region in each rod are measured. The indexing is done by machining a small length near one end to a smaller diameter than the rest of the rod.

The velocity of sound in the indexed region can then be calculated from a knowledge of the length of this region and the transit time in it. Both shear wave velocities and longitudinal velocities are determined. Any of the elastic moduli, e.g., Young's modulus, Poisson's ratio, shear modulus, can be determined if the sound velocities are known.

A new vacuum furnace for these measurements has been constructed and placed in operation. The temperature capability of this equipment is $>2500^\circ\text{C}$. The new equipment offers improvement over the older equipment both in terms of temperature capability (the old furnace was useful to about 1100°C), and in terms of a reduced temperature gradient across the sample. The development of the technique and the equipment for these measurements is therefore, essentially completed. The equipment will continue to be used to determine high temperature properties of materials of interest. Examples of some recent efforts in this area are given below.

The study of elastic properties of different samples of Type 304 and Type 316 stainless steels has continued. The intention of this study was to determine the variability of these properties in commercially available structural material. So far, three different rods of Type 304 stainless steel have been studied, and their moduli calculated. Two of these were done in the old furnace, which allows large thermal gradients to be present in the specimen, and one was run in the new high-temperature furnace, in which the gradients can be controlled. The study, while not far enough along to show how much variation might reasonably be expected from sample to sample, has shown that ultrasound echo patterns do vary from sample to sample, and that sound attenuation characteristics are not the same in each sample.

A rod of V-15w/oTi-7.5w/oCr was studied in the old vacuum furnace. The results of this study are compared with those of the study on V-20w/oTi (TV-20) that were reported in ANL-7119, and are given in Figure 171. It was also noticed that the attenuation of shear waves, as evidenced by the low amplitude of the "trailing pulses" generated by mode conversion in the index region of the rod, was significantly higher in the ternary alloy than in the binary. No explanation of this is available yet.

Measurements were also made on V-15w/oTi-7.5w/oCr at room temperature to discover the effect of annealing temperature on the moduli. The elastic moduli were determined from knowledge of the velocities of longitudinal and shear ultrasonic pulses. The apparatus described in ANL-7135 was used to measure the transit

Fig. 171. Elastic Moduli of V-15Ti-7.5Cr Compared to those of V-20Ti. Poisson's ratio is given in the top curve, Young's modulus in the center curve, and the shear modulus at the bottom.

TABLE 69. ROOM TEMPERATURE ELASTIC PROPERTIES OF V-15w/oTi-7.5w/oCr AS A FUNCTION OF ANNEALING TEMPERATURE

Heat Treatment	Density (g/cm ³)	Longitudinal Velocity (10 ³ cm/sec)	Shear Velocity (10 ³ cm/sec)	σ	μ (10 ¹¹ dyne/cm ²)	E (10 ¹¹ dyne/cm ²)	E (10 ³ kg/mm ²)
As-rolled	5.878 ± 0.001	6.08 ± 0.04	2.75 ± 0.01	0.371 ± 0.002	4.45 ± 0.03	12.19 ± 0.09	12.42 ± 0.09
700°C Anneal	5.88 ± 0.01	6.12 ± 0.02	2.748 ± 0.008	0.374 ± 0.004	4.44 ± 0.03	12.20 ± 0.09	12.44 ± 0.09
900°C Anneal	5.89 ± 0.01	6.008 ± 0.004	2.771 ± 0.007	0.365 ± 0.001	4.52 ± 0.02	12.35 ± 0.07	12.60 ± 0.07
1250°C Anneal	5.91 ± 0.01	6.10 ± 0.01	2.827 ± 0.006	0.363 ± 0.002	4.72 ± 0.02	12.88 ± 0.07	13.14 ± 0.07
1500°C Anneal	5.93 ± 0.01	6.02 ± 0.02	2.845 ± 0.005	0.356 ± 0.001	4.80 ± 0.01	13.02 ± 0.06	13.28 ± 0.06

σ = Poisson's Ratio; μ = Shear Modulus; E = Young's Modulus.

times of longitudinal pulses and shear pulses traveling from one face to the other in the disc-shaped specimens. The velocity was calculated by dividing the thickness of the sample by the transit time.

Four coupons of V-15w/oTi-7.5w/oCr, each about 0.15 cm (60 mils) thick, were made into discs 1.9 cm ($\frac{3}{4}$ -inch) in diameter. The faces were made parallel (to within 0.003 cm) and polished. The transit times, lengths, and densities of the four samples were measured while all four of them were still in the as-rolled condition. Then they were all annealed, each at a different temperature, for one hour at 10^{-6} torr. The samples were re-polished and the transit times, lengths,

and densities re-measured. The results are shown in Table 69. The values given for the as-rolled condition are averages over all four specimens.

The values of E and μ show a slight increase with increasing annealing temperature, while σ decreases. The largest difference between values of Young's modulus is 0.83×10^{11} dynes/cm², or about 6.5%.

b. ULTRASONIC INSTRUMENT AND TRANSDUCER DEVELOPMENT (R. H. SELNER)

Further progress on the investigation of the potential of porous metals as backing media for lead zirconate-titanate transducers has been made. Evaluation of

FIG. 172. Acoustic Impedance as a Function of Theoretical Density for Type 316 Stainless Steel and Nickel.

Type 316 stainless steel (316 SS) and nickel has been completed. A study of tungsten is now in progress.

As mentioned in the Annual Report for 1965, a backing material should transfer and absorb most of the energy from the back face of the transducer.⁽¹²³⁾ Maximum transfer of energy is accomplished when the acoustic impedances (ρv) of the transducer and backing medium are equal. Absorption or attenuation of ultrasound in porous metals varies directly with porosity.

For a particular particle size of either Type 316 stainless steel or nickel, an acoustic impedance that equals the impedance of a typical lead zirconate-titanate ($34 \times 10^5 \text{ gm cm}^{-2}\text{-sec}^{-1}$ for Clevite's PZT-4) can be achieved. Impedance matching occurs at high densities in coarse-particle samples and at somewhat lower densities in fine-particle samples because the longitudinal velocity (v), in general, varies indirectly with particle size. The effect of the theoretical density on acoustic impedance for -325 and -500 mesh nickel and for -325 mesh 316 SS is shown in Figure 172. Note that the theoretical density required to achieve an impedance value of $34 \times 10^5 \text{ gm cm}^{-2}\text{-sec}^{-1}$ varies from 79% to 83% in these fine-particle samples. Theoretical densities as high as 90% are required for matching when coarser particles are used.

Ultrasonic probes with lead zirconate-titanate elements and a variety of porous 316 SS or nickel back-

ings have been constructed. In probes with matched or closely matched backings, a series of pulses follow the initial generated pulse. These trailing pulses are reflections from the back surface of the backing member. Reduction and scattering of the trailing pulses, which limit the resolution capabilities of a probe, is accomplished by the introduction of a conical rear face in the backing member.⁽¹²⁴⁾ Backing members of -500 mesh nickel and with conical rear faces are the most effective, especially at frequencies of 5 Mc and up. At lower frequencies, the trailing pulses are not sufficiently attenuated.

Preliminary results on three porous tungsten samples indicate that tungsten with theoretical densities below 70% will be required to obtain an impedance match with lead zirconate-titanate. Expectations are that the trailing pulses will be eliminated or greatly reduced in amplitude in a matched backing of porous tungsten. Additional samples of tungsten have been ordered for evaluation purposes.

c. DEVELOPMENT OF A NEUTRON-IMAGE INTENSIFICATION SYSTEM (H. BERGER)

Significant improvements in the performance capability of the thermal neutron image intensifier tube,⁽¹²⁵⁾

⁽¹²⁴⁾ Howry, D. H., et al., *Uni-directional Ultrasonic Transducer*, U. S. Patent 2,972,068, February 14, 1961.

⁽¹²⁵⁾ Berger, H., Niklas, W. F., and Schmidt, A. *An Operational Thermal Neutron Image Intensifier*, J. Appl. Phys., **36**, 2093-2094 (1965).

⁽¹²³⁾ Annual Report for 1965, Metallurgy Division, ANL-7155, p. 160.

FIG. 173. Light Yield of a New, 15 cm Diameter Target Neutron Image Intensifier Tube.

45428

and of a complete thermal neutron television imaging system⁽¹²⁶⁾ have been achieved during the past year. These improvements have been achieved with the continued cooperation of the Rauland Corporation. The newest intensifier tube provides improved response⁽¹²⁷⁾ over former tubes in terms of light yield and relative neutron-gamma response, and also has the advantage of reduced physical size. The improved response of the complete television system results from these tube improvements and from the fact that an image orthicon television system has been available for test.

The operating principles of the intensifier tube remain unchanged.⁽¹²⁵⁾ The neutron imaging beam is detected within the evacuated image intensifier tube by a large diameter neutron scintillator. The scintillator is positioned adjacent to a photo-emissive layer and electrons are released from this layer in proportion to the neutron intensity at any given point on the scintillator. These electrons are focused by an electron lens upon a small phosphor screen at the output end of the tube and simultaneously accelerated by a high voltage. A bright, demagnified visible image appears at the output phosphor. The light signal can be detected by direct obser-

vation, or by means of optical or closed-circuit television systems.

The visible image is much brighter than a neutron scintillator would appear, with the same neutron irradiation, because of the gain achieved by the voltage acceleration of the photoelectron signal, and by the minification of the image. X-ray image intensifier tubes, which operate similarly, achieve brightness gain factors in the order of 4000 if one compares the brightness of the intensifier tube output screen to that of a standard X-ray fluoroscopic screen stimulated by the same X-ray intensity and quality. In the neutron case, such brightness gain figures have less meaning because neutron fluoroscopy is not a standard technique. However, the gain of the neutron image intensifier tube is great enough so that the quantum limitation of the detection process results from the neutron absorption and utilization in the neutron scintillator. The brightness gain of the most recent image intensifier tube over that of a commercially available neutron scintillator⁽¹²⁸⁾ (Nuclear Enterprises, Ltd., Type NE 421) is approximately 2×10^4 .

The light yield of the newest neutron image intensifier tube is shown in Fig. 173. The tube yields an output phosphor brightness of about 100 ft.-Lamberts for an incident thermal neutron intensity of 2×10^7

⁽¹²⁶⁾ Berger, H., *Characteristics of a Thermal Neutron Television Imaging System*, Materials Evaluation, **24**, 475-481 (Sept., 1966).

⁽¹²⁷⁾ Dolon, P., Berger, H., and Niklas, W. F., *An Improved Neutron Image Intensifier Tube*, to be published in Proc. 13th Nuclear Science Symposium, held in Boston, Oct. 19-21, 1966.

⁽¹²⁸⁾ Wang, S. P., Shull, C. G., and Phillips, W. C., *Photography of Neutron Diffraction Patterns*, Rev. Sci. Instr., **33**, 126 (1962).

n/cm²-sec. The improved light output from the new intensifier tube is approximately five times greater than that achieved from the first tube studied on this program.⁽¹²⁴⁾ Although part of the difference in gain can be attributed to normal tube-processing variables, a major portion of the improvement is attributed to the use of ZnS(Ag) phosphor in the neutron scintillator of the tube, rather than the ZnCdS(Ag) phosphor used in the first tube.

The neutron scintillator is composed of a mixture of LiF powder (95.72% Li-6 enriched) and phosphor powder, in a weight ratio of 4 parts phosphor to 1 part LiF.⁽¹²⁹⁾ The ZnCdS(Ag) phosphor in the initial tube was used because it is a phosphor normally used in X-ray image intensifier tubes. It provides improved response to X-radiation in spite of a spectral mismatch between the phosphor and the photoemissive layer, because of the higher density and resulting improved X-ray absorption. The substitution of ZnS(Ag) phosphor in the neutron scintillator provides improved neutron response because of the better spectral match of this phosphor with the photoemissive layer.

The new phosphor also provides an improvement in the relative neutron-gamma response of the intensifier tube, because of the decreased gamma absorption of the ZnS(Ag) material. Tests indicate that the new tube provides a more favorable neutron-gamma response as compared to the older tube, by a factor of at least two. A cobalt-60 gamma intensity of 600 R/hr. provides an intensifier-tube output signal equal to that produced by a thermal neutron intensity of 10⁶ n/cm²-sec. The new tube has provided useful neutron radiographic television images of reactor fuel samples even in the presence of gamma radiation intensities⁽¹²⁹⁾ as high as 10,000 R/hr., when used with the thermal neutron beam intensity available at Argonne's Juggernaut reactor facility. This facility provides a thermal neutron intensity of 2×10^7 n/cm²-sec, over a 6.3×10 cm area.

One additional change should be noted, even though it does not specifically have to do with the performance of the tube. The size of the tube has been reduced so that the sensitive diameter of the tube is now 15 cm, rather than 22 cm. This results in a much more compact tube and permits its application in areas in which the larger size may have imposed a problem. The 15 cm dia. image is more than sufficient for most neutron imaging situations. A neutron image intensifier tube having a useful target diameter of 7.5 cm is being considered for a dynamic neutron inspection problem in-

volving a study of heat pipes at Princeton University.⁽¹³⁰⁾

The high contrast resolution capability of the new tube is similar to that previously reported⁽¹³¹⁾ for intensifier tube number two. This is dependent upon many factors. As determined with the above mentioned beam facility, the resolution of the system is dependent upon the divergence of the neutron beam itself, the thickness of the neutron scintillator layer in the intensifier tube, and the spacing of the scintillator layer from the tube window. This latter factor, which determines the closest usable object-detector distance, has been reduced to a value less than 1 cm in the new tube. The result of this spacing reduction has been to reduce the influence of the divergence of the neutron beam and to improve the capability for high-contrast resolution to a limit imposed by the thickness of the scintillator itself. That thickness, and the new tube resolution capability are each approximately 0.35 mm; the first tube resolved hole sizes 0.5 mm or larger in diameter.

Another factor involved in resolution capability is the thermal neutron intensity incident on the tube. The detail and contrast which can be detected are each limited by the statistical variation in the neutron imaging beam. Therefore, the size of a neutron spot which can be detected depends upon the number of neutrons actually contributing to the image during the time the image information is accumulated, and upon the quantum variation in the image which will permit observation of the signal.

For visual observation of the neutron image at the output phosphor of the intensifier tube, one can use the following factors: accumulation time of the signal is 0.2 sec (a figure normally used for the accumulation time of the human eye);^(132,133) number of neutrons contributing to the image is 15 per cent of those incident on the intensifier tube (allowing 50% absorption in the intensifier tube window and 30% useful absorption in the neutron scintillator); minimum observable signal-to-noise ratio^(132,133) is 3. Neutron beams (at essentially 100% contrast) that should be visible under these conditions are shown in Figure 174. Neutron beam sizes that should be detectable lie above the line B, those which should not be detectable lie below line B. The straight line A, for a beam size of 0.35 mm di-

⁽¹³⁰⁾ Moss, R. A., Princeton University, private communication, 1966.

⁽¹³¹⁾ *Annual Report for 1965, Metallurgy Division*, ANL-7155, pp. 160-163.

⁽¹³²⁾ Sturm, R. E., and Morgan, R. H., *Screen Intensification Systems and Their Limitations*, Am. J. Roentgenology and Radium Therapy, **62**, 617 (1949).

⁽¹³³⁾ Morton, G. A., *Image Intensifiers and the Scotoscope*, Applied Optics, **3**, 351 (1964).

⁽¹²⁹⁾ Berger, H., and Beck, W. N., *Neutron Television System Inspection of Radioactive Fuel Capsules*, Trans. Am. Nucl. Soc., **9**, No. 2, 597 (Oct., 1966).

45427

FIG. 174. Neutron Beam Sizes that Should Be Detectable for a Given Neutron Intensity with a Neutron-image Intensifier Tube Are Shown. Points above line B should be observed; those below line B should not. Line C represents the improvement to be expected if the neutron absorption in the window of the intensifier tube were eliminated, and line D represents the ideal case in which all the incident neutrons contribute to the image. Line A is the resolution limit of the present tube (0.35 mm). The experimental data, obtained by direct observation of the intensifier tube output screen with a $3\times$ optical system, correlate well with lines A and B, the predicted threshold values for this intensifier tube.

ameter, is the limiting resolution of the present image intensifier tube. Line C represents the shift in the visible-not visible dividing line if the neutron attenuation in the image intensifier tube window could be eliminated. In that case, 30% of the incident neutrons would contribute to the image. This represents a situation which should be possible. Line D represents the improvement which would be possible if all of the incident neutrons contributed to the image, the ideal situation.

Also shown in Figure 174 is an experimental curve obtained in a test in which the output phosphor screen was directly observed through a binocular optical system⁽¹³⁴⁾ by several dark adapted observers. The neutron beam sizes reliably observed at several neutron intensities are shown; the data correlate well with the dividing line formed by lines A and B. For neutron beams of reasonable size, one can actually see, with the intensifier tube, neutron images for thermal neutron intensities of 100 n/cm²-sec or greater. Some direct observations have been made for incident intensities as low as 50 n/cm²-sec.

The increased brightness yield of the new intensifier tube has also resulted in improved television response. Television images with a closed circuit vidicon system

can be observed for incident thermal neutron intensities as low as 2×10^4 n/cm²-sec. With a more sensitive image orthicon television system,⁽¹³⁵⁾ thermal neutron intensities as low as 200 n/cm²-sec have been observed by a television presentation. Of course, the production of useful images with such low neutron intensities would require some storage element in the system, in order to decrease the statistical variations. The image orthicon system has also provided an advantage in observed speed of response of the neutron television system, in that it is a faster response tube than the vidicon. High-contrast object motion as fast as 15 m/min. has been followed with the image orthicon system, a factor three times better than that obtained with the vidicon system.

In the area of applications, the dynamic nature of the detection technique permits one to observe moving systems. Motion applications have included the post-irradiation inspection⁽¹²⁶⁾ of heated reactor fuel materials (including the observation of the rupture of fuel jacket materials) and the observation of water flow and bubble patterns in metal assemblies. The latter study, involving a simulated water fluid heat pipe, provided excellent contrast of the water-bubble patterns. A more thorough study of the heat-pipe system

⁽¹³⁴⁾ The optical system for these tests was loaned to us by the Picker X-Ray Corp.

⁽¹³⁵⁾ The image orthicon television system was made available for these tests by the Idaho Division, ANL.

TABLE 70. FUEL PIN CP-1-6 AVERAGE BURNUP 0.32 a/o

	First Run				Second Run			
	α (cm ² /sec)	% Change	K (cal cm/cm ² sec °C)	% Change	α (cm ² /sec)	% Change	K (cal cm/cm ² sec °C)	% Change
1st Transverse Cut	0.0620	0.6	0.0473	4.0	0.0609	1.14	0.0433	4.8
1st Longitudinal Cut	0.0583	5.6	0.0397	12.7	0.0598	2.9	0.0399	12.3
2nd Transverse Cut	0.0608	1.1	0.0399	12.3	0.0612	0.64	0.0406	10.8
2nd Longitudinal Cut ^(a)	0.0529		0.0367		0.0575		0.0384	
3rd Transverse Cut	0.0558	9.4	0.0375	18.9	0.0536	12.6	0.0370	18.7
3rd Longitudinal Cut	0.0533	13.5	0.0351	22.8	0.0542	12.0	0.0360	21.0
4th Transverse Cut	0.0616	0	0.0392	13.8				

^(a) Specimen had a crack; values are not accurate.

TABLE 71. FUEL PIN ANL-6-115-5, AVERAGE BURNUP 1.8 a/o

	First Run				Second Run			
	α (cm ² /sec)	% Change	K (cal cm/cm ² sec °C)	% Change	α (cm ² /sec)	% Change	K (cal cm/cm ² sec °C)	% Change
1st Transverse Cut	0.0556	9.5	0.0378	16.9	0.0558	9.4	0.0380	16.5
1st Longitudinal Cut	0.0538	12.7	0.0347	23.7	0.0534	13.3	0.0351	22.9
2nd Transverse Cut	0.0549	10.9	0.0330	27.9	0.0558	9.4	0.0379	16.7
2nd Longitudinal Cut	0.0537	12.8	0.0355	23.4	0.0526	14.6	0.0352	22.6
3rd Transverse Cut	0.0554	10.6	0.0368	19.1	0.0566	8.1	0.0372	18.4
3rd Longitudinal Cut	0.0539	12.5	0.0331	27.8	0.0534	13.3	0.0348	23.5
4th Transverse Cut	0.0272	55.8	0.0198	56.5	0.0264	57.5	0.0203	55.4
5th Transverse Cut	0.0532	13.6	0.03548	21.9				

is now planned at Princeton University.⁽¹³⁰⁾ Other neutron imaging applications, involving still objects, are obviously also possible, and in such cases the television technique provides the significant advantage of presenting the image immediately. This has been used to advantage in several neutron radiographic problems. The fast television presentation has been used to determine the most useful area and orientation of the inspection object for a final, high-resolution radiograph. Finally, in the area of application, the intensifier tube can be of value in many neutron problems. The determination of the shapes and locations of neutron beams, observations to determine the proper placement of a sample in a neutron beam, and observation of neutron-diffraction patterns are examples of such application areas.

d. INFRARED SYSTEMS FOR NONDESTRUCTIVE TESTING (I. R. KRASKA)

Some improvements in the infrared radiometer equipment previously described⁽¹³⁶⁾ have been made. A cooled (by means of a thermoelectric cooler) indium antimonide photoelectromagnetic detector has been used in the radiometer. This detector provides faster

response than the thermistor detector previously used. The time constant of the indium antimonide detector is less than 1 μ sec. Scan speeds up to 20 cm/min have been used successfully.

This detection system, with a radiant heater (as previously described),⁽¹³⁶⁾ and a mechanical translation system have been used to infrared test a number of inspection objects, including stainless steel and aluminum-clad flat reactor fuel plates, and sodium-bonded fuel capsules. The test results compared well to those achievable by other test methods, except that ultrasonic methods appeared to be capable of better resolution. Tests indicated that in stainless steel-clad flat fuel plates, and sodium-bonded fuel capsules, unbonded areas of 3 mm and greater could be detected by the infrared radiometer when transient heating was used.

These comparisons of the infrared test technique with other nondestructive test methods, as applied to typical reactor materials, provide the final information desired from this program. Experience with the infrared method has been gained. Among the advantages of this technique are its speed of response and the fact that its use does not require physical contact with the test sample. The technique can now be applied to inspection problems, as appropriate.

⁽¹³⁶⁾ Annual Report for 1965, Metallurgy Division, ANL-7155, p. 165.

TABLE 72. FUEL PIN ANL-6-113-2 AVERAGE BURNUP 3.0 a/o

	First Run				Second Run			
	α (cm ² /sec)	% Change	K (cal cm/cm ² sec °C)	% Change	α (cm ² /sec)	% Change	K (cal cm/cm ² sec °C)	% Change
1st Transverse Cut	0.0478	22.4	0.0290	36.3	0.0463	24.8	0.0270	40.6
1st Longitudinal Cut	0.0348	45.1	0.0238	46.9	0.0342	44.8	0.0243	44.4
2nd Transverse Cut	0.0553	10.2	0.0355	23.4	0.0548	11.0	0.0355	23.4
2nd Longitudinal Cut	0.0309	49.8	0.0215	52.7	(a)			
3rd Transverse Cut	0.0462	25.0	0.0311	32.6	0.0475	22.8	(b)	
3rd Longitudinal Cut	0.0454	26.2	0.0293	33.4	(b)			
4th Transverse Cut	0.0475	22.8	0.0301	33.8	0.0480	22.1	0.0303	34.3

(a) Specimen broke before the second run.

(b) Specimen oxidized.

TABLE 73. THERMAL DIFFUSIVITY AND THERMAL CONDUCTIVITY FOR FIVE SAMPLES CUT FROM SAMPLE PLATE A

$T(^{\circ}\text{C})$	$\alpha(\text{cm}^2/\text{sec})$	$K(\text{cal cm/cm}^2 \text{ sec } ^{\circ}\text{C})$	$T(^{\circ}\text{C})$	$\alpha(\text{cm}^2/\text{sec})$	$K(\text{cal cm/cm}^2 \text{ sec } ^{\circ}\text{C})$
Sample #1			Sample #2		
25	0.0245	0.0252	27	0.0256	0.0266
101	0.0246	0.0254	101	0.0260	0.0276
192	0.0250	0.0263	202	0.0265	0.0291
305	0.0261	0.0277	304	0.0265	0.0294
400	0.0262	0.0280	398	0.0278	0.0310
499	0.0275	0.0290	499	0.0280	0.0317
604	0.0284	0.0305	596	0.0290	0.0296
711	0.0284	0.0317	698	0.0295	0.0335
798	0.0291	0.0325	796	0.0302	0.0343
Sample #3			Sample #4		
28	0.0245	0.0250	29	0.0264	0.0276
105	0.0251	0.0258	104	0.0269	0.0282
197	0.0254	0.0260	207	0.0280	0.0308
301	0.0259	0.0275	303	0.0266	0.0297
400	0.0267	0.0288	399	0.0280	0.0315
497	0.0275	0.0295	500	0.0291	0.0320
603	0.0280	0.0308	596	0.0299	0.0330
703	0.0284	0.0315	702	0.0305	0.0341
786	0.0285	0.0320	787	0.0302	0.0345
$T(^{\circ}\text{C})$	$\alpha(\text{cm}^2/\text{sec})$	$K(\text{cal cm/cm}^2 \text{ sec } ^{\circ}\text{C})$			
Sample #5					
26	0.0268	0.0272			
96	0.0278	0.0279			
198	0.0326	0.0314			
301	0.0277	0.0283			
402	0.0285	0.0295			
499	0.0299	0.0321			
599	0.0304	0.0340			
700	0.0307	0.0341			
801	0.0310	0.0338			

TABLE 74. THERMAL DIFFUSIVITY AND THERMAL CONDUCTIVITY FOR FIVE SAMPLES CUT FROM PLATE B

$T(^{\circ}\text{C})$	$\alpha(\text{cm}^2/\text{sec})$	$K(\text{cal cm}/\text{cm}^2 \text{ sec } ^{\circ}\text{C})$	$T(^{\circ}\text{C})$	$\alpha(\text{cm}^2/\text{sec})$	$K(\text{cal cm}/\text{cm}^2 \text{ sec } ^{\circ}\text{C})$
Sample # 1			Sample # 2		
26	0.0144	0.0142	25	0.0152	0.0149
101	0.0140	0.0138	99	0.0146	0.0143
199	0.0132	0.0123	203	0.0131	0.0136
302	0.0125	0.0135	301	0.0132	0.0137
400	0.0118	0.0123	399	0.0121	0.0124
497	0.0114	0.0122	497	0.0119	0.0121
599	0.0112	0.0119	597	0.0112	0.0126
700	0.0121	0.0114	695	0.0110	0.0123
801	0.0111	0.0116	802	0.0117	0.0122
Sample # 3			Sample # 4		
25	0.0153	0.0154	26	0.0150	0.0158
99	0.0148	0.0147	101	0.0146	0.0153
198	0.0136	0.0140	200	0.0135	0.0147
299	0.0127	0.0135	297	0.0132	0.0137
398	0.0114	0.0132	399	0.0121	0.0135
500	0.0114	0.0129	498	0.0118	0.0130
600	0.0112	0.0127	601	0.0115	0.0126
698	0.0117	0.0139	699	0.0111	0.0125
806	0.0108	0.0125	799	0.0111	0.0122
$T(^{\circ}\text{C})$		$\alpha(\text{cm}^2/\text{sec})$	$K(\text{cal cm}/\text{cm}^2 \text{ sec } ^{\circ}\text{C})$		
Sample # 5					
27	0.0151		0.0156		
100	0.0146		0.0154		
206	0.0137		0.0146		
300	0.0132		0.0145		
399	0.0125		0.0138		
503	0.0119		0.0133		
597	0.0117		0.0130		
700	0.0114		0.0138		
802	0.0114		0.0126		

e. MEASUREMENT OF THERMAL CONDUCTIVITY OF IRRADIATED FUEL AS A FUNCTION OF BURNUP AND TEMPERATURE (R. A. DI NOVI)

The thermal-pulse method⁽¹³⁷⁾ of measuring thermal diffusivity and thermal conductivity is being utilized to determine these properties for irradiated fuel pins. Details of the method^(138,139) and the results⁽¹⁴⁰⁾ on unirradiated uranium-fissium alloys were previously reported.

The uranium-5w/oFs alloy was selected for post-irradiation studies. Room-temperature measurements on three fuel pins of this alloy, with average burnups of 0.32 a/o, 1.8 a/o, and 3.0 a/o, have been completed.

Results of the thermal-diffusivity and thermal-conductivity measurements on irradiated U-5w/oFs fuel pins are given in Tables 70, 71, and 72. Each fuel pin was alternately cut into transverse and longitudinal sections. Transverse cuts produce sections for measuring thermal properties in the axial direction; longitudinal cuts produce sections for measuring thermal properties in the radial direction. The measured diffusivity and conductivity of the unirradiated U-5w/oFs from which the percentage changes in the tables calculated are:

$$\alpha = 0.0616 \text{ cm}^2/\text{sec}$$

$$K = 0.0455 \frac{\text{cal/cm}}{\text{cm}^2\text{sec}^\circ\text{C}}$$

Several conclusions are immediately evident from these results:

(a) The thermal diffusivity and conductivity are functions of burnup.

(b) There is, generally, a greater change in both

⁽¹³⁷⁾ Parker, W. J., Jenkins, R. J., Butler, C. P., and Abbott, G. L., *Flash Method for Determining Thermal Diffusivity, Heat Capacity and Thermal Conductivity*, J. Appl. Phys., **32**, 9, 1679 (1961).

⁽¹³⁸⁾ *Annual Report for 1963, Metallurgy Division, ANL-6868*, pp. 221-222.

⁽¹³⁹⁾ *Annual Report for 1964, Metallurgy Division, ANL-7000*, p. 146.

⁽¹⁴⁰⁾ *Annual Report for 1965, Metallurgy Division, ANL-7155*, p. 166.

these properties in the radial direction than in the axial direction.

(c) Both of these properties vary along the length of the fuel pin.

(d) For any one specimen, irradiation produced a greater decrease in its conductivity than in its diffusivity.

Measurements on the irradiated alloys are planned for temperatures up to 600°C. A vacuum furnace suitable for remote operation has been designed and built, and a vacuum system capable of operating to 10⁻⁷ torr has been constructed. This system has been thoroughly tested, and will shortly be installed in a cave area.

As part of the test for the sample vacuum furnace, before installation in the cave, thermal diffusivity (α) and thermal conductivity (K) of twenty samples of UO₂-SS₃₄₇ cermet fuel plates were measured from ambient temperature to 800°C. The twenty specimens were cut from four fuel plates, obtained from three different fabricators. The plates were fabricated for the AARR program. The core of the plate was 0.75 mm (0.030 in.) thick; the SS₃₄₇ clad was 0.125 mm (0.005 in.) thick. The composition of the cermet fuel varied from 37w/oUO₂-SS₃₄₇ to 40.4w/oUO₂-SS₃₄₇.

A typical result of the measurements is shown in Table 73. In this case, as in the case of the specimens cut from three of the fuel plates, α and K were found to be increasing functions of temperature. The five samples from any one fuel plate gave measured values agreeing to $\pm 5\%$, and differences between the average values of the fuel plates were 10 to 15%. These differences in thermal properties of the fuel plates depend not only on the core composition (impurity composition and percentages greatly vary), but also on the quality of the bonds between core and the clad.

One plate, results for which are shown in Table 74, exhibited thermal properties that decreased with increasing temperature; measured values were also relatively low. Metallographic results show this plate to be extremely stringered. It was included in the test to enable an evaluation of the effect of poor dispersion on thermal conductivity to be made. The unusual results on this plate are due to its poor dispersion properties.

4. Development of Techniques and Equipment for Alpha-Gamma Hot Cell

a. DEVELOPMENT OF METALLOGRAPHIC TECHNIQUES FOR IRRADIATED PLUTONIUM FUELS (R. CARLANDER)

A remote alpha-gamma shielded metallograph was constructed and attached to the Alpha-Gamma Hot

Cell for the microscopic examination of high burnup plutonium-bearing fuel specimens. The instrument was designed to provide complete alpha containment, maximum accessibility for adjustment or repairs, and full protection against hard gamma radiation from fission

106-9176

FIG. 175. Relationship of Glovebox to Alpha-Gamma Metallograph during Construction.

products. The metallograph was assembled, therefore, as three distinct but interrelated units: an inert-atmosphere glovebox chamber, a specimen-transfer system, and a steel shield.

The inert-atmosphere glovebox concept was selected to isolate in one small area only those parts subject to alpha contamination, thereby providing convenient maintenance of the majority of the microscope components and controls and was modeled to some extent after that incorporated in the Bausch and Lomb Glovebox Type Research Metallograph. In the commercial instrument, the objective and specimen stage are enclosed in a glovebox which is mounted on a plate over the body of the microscope. The optical path through the objectives is made alpha-tight by sealing a circular optical glass in an opening in the microscope plate directly below the objectives; the objectives are corrected for the increase in tube length required by this modification. Objectives were mounted in individual holders and were manually replaced through a gloveport.

In the Argonne-designed alpha-gamma metallograph, individual objective selection was replaced with an objective turret, similar to that used in the Bausch and Lomb alpha-gamma blister-type remote metallograph. The turret contained 5 $\times$, 20 $\times$, and 40 $\times$ non-browning objectives and a 50 $\times$ fluorite objective—all optically corrected for the increase in tube length associated with the disc of optical glass mounted in the

microscope plate. The turret rotation in the Bausch and Lomb metallograph was controlled through mechanical linkages. The rotation in the Argonne metallograph is electrically controlled to facilitate remote operation. The stage rotation and x- and y-translations are similarly modified. The microscope during an early stage of assembly is shown in Figure 175.

In order to isolate the shielded glovebox from the Hot Cell, the specimen transfer system was designed with the capability of complete withdrawal into the cave wall. A specimen basket, which rides on a link chain mounted on two sprockets, transports the metallographic specimens from the cave interior to the microscope stage (Figure 176). The specimen remains in the specimen basket during all phases of the metallographic examination, and the basket is supported on a ball swivel chain to accommodate the stage rotation and x- and y-translations.

The gamma shield was machined from 8-inch thick steel blocks and was assembled around the glovebox and the body of the microscope. Since the shield was of a building block construction, it was not necessary to remove the entire shield to service the majority of the microscope parts. The microscope and remaining microscope components (field diaphragm, filters, oblique lighting, etc.) were purchased in the commercially-designed condition and were then provided with access shafts for the various controls (Figure 177).

The assembled metallograph is shown in Figure 178. The camera station and illuminating unit are standard equipment. The right-angle-bend optical relay from the microscope to the camera at the left in Figure 178 was necessary since extension of the camera and camera bellows parallel to the Hot Cell wall would interfere with other operations in the immediate area.

b. AUTORADIOGRAPHY (B. J. KOPROWSKI, F. L. BROWN, AND C. H. GEBO)

Autoradiography is being used as a technique for the postirradiation examination of the microstructure of fuel elements for fission-product distribution. Two complementary techniques are used in the Alpha-Gamma Hot Cell: (1) alpha autoradiography for plutonium distribution, and (2) beta-gamma autoradiography for fission-product distribution.

In the alpha-autoradiographic process, alpha particles emitted from a fuel specimen enter a plastic film of cellulose nitrate, which is placed in direct contact

with the fuel specimen, causing a deformation (alpha tracks) in the film. Subsequent etching of the film with sodium hydroxide removes the deteriorated areas and provides a film that can then be used as a negative for further photographic reproduction. The photograph, shown in Figure 179, is an autoradiograph of a (U, Pu)C fuel specimen that had been prepared in a plastic metallurgical mount, ground and polished, in preparation for metallographic examination. The autoradiograph, which was produced in what has now become a routine step in the metallographic examination of fuel specimens, shows excellent contrast between the alpha-emitting PuC phase and the UC phase.

Beta-gamma autoradiographs are prepared in much the same way as alpha-autoradiographs. Fuel specimens that have been prepared in plastic mounts for metallographic examination are, again as a routine step in this phase of the examination, placed in contact with a sealed envelope containing a Kodak High Resolution film plate. The glass plate containing the emulsion is wrapped in a thin aluminum foil (0.0007 in.) and the foil-wrapped plate is then inserted in a regular manila envelope into which has been inserted a thin "window" of Mylar foil (0.0025 in.). After the photographic plate has been exposed to the radioactive fuel sample, through the aluminum and Mylar foils, the sealed envelope is removed from the hot cell. After a decontamination process, the film packet is removed from the envelope and developed by normal darkroom techniques. Figure 180 illustrates an autoradiograph of a UO_2 fuel specimen produced by this technique.

The removal from the hot cell and the decontamination of the cellulose nitrate film and the Kodak High Resolution film packet have not caused any undue difficulty nor required any unusual handling procedures. Both types of film are removed from the hot cell in a plastic transfer pouch, taken to a fume hood and removed from the pouch. The cellulose nitrate film is normally decontaminated when it is etched in sodium hydroxide; the sodium hydroxide, of course, is disposed of as an active liquid waste. For the beta-gamma autoradiographs, the foil-wrapped film is carefully removed from the envelope and, if properly done, can be taken to a darkroom for developing without any further decontamination procedures. The envelope is contaminated and is handled as dry active waste.

c. REPLICATION FOR ELECTRON MICROSCOPY (B. J. KOPROWSKI, Y. K. YOON, H. WATANABE,* AND C. H. GEBO)

A negative reproduction of a ground and polish irradiated fuel specimen can be obtained on a plastic

106-9172

FIG. 176. Metallograph Specimen Transfer System and Specimen Bucket.

*Now at Japan Atomic Energy Research Institute, Tokai, Japan.

106-9173

FIG. 177. Microscope and Associated Controls.

106-8961

FIG. 178. Remote Alpha-Gamma Metallograph, Illumination System, and Camera Station.

EI-5760

FIG. 179. Alpha Autoradiograph of Fuel Specimen Containing Irradiated (U,Pu)C.

16×

EI-5761

5½×

FIG. 180. Beta-Gamma Autoradiograph of a Specimen Containing Irradiated UO_2 .

EI-5762

FIG. 182. Comparison of a Gamma Scan and Neutron Radiograph of a Jacketed Fuel Assembly.

121226

FIG. 181. Electron Photomicrograph of a Replica of a (U,Pu)C Fuel Specimen Showing Particles in UC.

film that can be used to produce a secondary carbon replica, which is suitable for electron microscopy. Primary replicas of irradiated fuel specimens containing alpha-active materials are being prepared in the Alpha-Gamma Hot Cell in the following manner:

- (1) A film of acetyl cellulose dipped in acetone is placed on the polished fuel specimen to remove any loose particles and then removed.
- (2) A second film of acetyl cellulose (Bioden RFA) dipped in acetone is placed on the fuel specimen.

After a contact time of about one hour, the film is carefully removed from the fuel specimen, removed from the hot cell in a plastic transfer pouch and taken to a fume hood where it is decontaminated.

The primary acetyl cellulose replica is, first, shadowed at an oblique angle with an evaporated film of platinum-20% palladium alloy and then an evaporated carbon coating is deposited on the replica. These two steps are performed in an evacuated bell jar. Finally, the primary plastic replica is dissolved, leaving a sec-

ondary carbon replica which is suitable for examination in an electron microscope. An electron photomicrograph of a carbon replica showing particles in the UC phase of a (U,Pu)C fuel specimen, is shown in Figure 181.

d. GAMMA-ACTIVITY PROFILES OF IRRADIATED FUEL ELEMENTS (B. J. KOPROWSKI, V. G. SCOTTI, AND A. VANDERGUST)

Gamma scanning provides, in a relatively simple manner, a graphic profile that illustrates the relative intensity and distribution of fuel material within a jacketed fuel assembly.

The equipment developed for the Alpha-Gamma Hot Cell to provide this information consists of: (1) a fuel-element holder and traversing mechanism located within the hot cell, (2) a collimating orifice in a shield plug installed in the wall of the hot cell, (3) a scintillation counter and a multichannel pulse height analyzer located outside of the hot cell. During the examination, the specimen is driven at constant speed past the collimating orifice. The relative intensity of the gamma-ray beam emerging from the orifice is measured by the scintillation counter and simultaneously recorded. The composite photographs, shown in Figures 182 and 183 illustrate the correlation between the gamma profiles and neutron radiographs of the jacketed fuel elements.

The profiles obtained by this technique provide a basis for determining locations at which the fuel element should be sectioned for further metallurgical and radiochemical examination. The gross gamma scan when combined with the results from the subsequent examinations can be used to establish relative and average burnup profiles, and reactor neutron flux patterns. Variations in this basic technique, such as scanning at preselected energy levels, or scanning at a fixed point with the multichannel analyzer, can provide information concerning the migration or distribution of specific fission products.

EI-5763

FIG. 183 Comparison of a Gamma Scan and Neutron Radiograph Showing Excellent Correlation of Results

Part II

Basic Metallurgy

A. METALLURGY OF THE ACTINIDE METALS

1. Uranium

a. CRYSTAL STRUCTURE OF ALPHA PHASE

(M. H. MUELLER, L. HEATON, H. KNOTT, AND J. WILLIAMS*)

Although it was our intention to obtain three-dimensional neutron diffraction data from room temperature to liquid-helium temperature during the past year, this has not been possible since we were delayed in the completion of the Cryo-Orientor as indicated in the Diffraction Instrument section.

The purity of the monochromatic neutron beam from the germanium monochromator could, however, be checked by obtaining intensity measurements with a NaCl single crystal. These results showed a relative intensity of 1.6:100.0 for the (100) to the (200). The (100) of course should not be present in NaCl but could be due to a small quantity of $\lambda/2$ contaminant in the monochromatic beam. This check is important as $\lambda/2$ is a component of the small residual (001) intensity observed from α -uranium at room temperature even after correcting for double scatter within the uranium single crystal as discussed previously.⁽¹⁴¹⁾

As a further check on the presence of nonpermitted reflections in alpha uranium such as 00*l*, 0*k*0, and *h*00 where *h*, *k*, or *l* are odd, we have made a careful X-ray investigation at room temperature. A standard MgO single crystal, cleaved on a cube face, was used as a check for the $\lambda/2$ presence. Using a G.E. diffractometer, with a molybdenum tube, we determined that a window voltage between 3 to 5 volts gave a minimum $\lambda/2$ when we used 50 KV. The KV was then reduced in increments where it was determined that a reduction to a voltage slightly lower than 35 KV should and did eliminate all traces of $\lambda/2$ based on the lower wavelength limit. A redetermination of the window width indicated a 2 to 4 volt setting as the best. The molybdenum tube was then operated at 30 KV and 20 ma and 2θ scans made through the *h*00 reflections. Whereas a counting rate of over 33,000 cpm was obtained at the (200) peak only approximately 4 cpm were observed at the (100) position— $\lambda/2$ from the (200). The 4 cm rate prevails over approximately 10 degrees with no indication of a $\lambda/2$ peak.

A single alpha uranium crystal with orthogonal faces several mm on an edge was then aligned in place of the

MgO crystal. The *h*00, 0*k*0 and 00*l* scans were then made after realigning each crystal face. Peak counting rates obtained are summarized from α -U.

hkl	λ	$\lambda/2^*$
(200)	33116	84
(020)	8430	20
(002)	54321	48

* These counting rates prevailed over several degrees 2θ thus indicating no odd order reflections.

Low-temperature results similar to the above are needed with both X-rays and neutrons. It is anticipated that considerable difficulty will be encountered with the $\lambda/2$ neutron component unless a mechanical velocity selector is constructed or suitable filters are found for wavelengths of approximately 2–2.5Å. Some improvement of λ to $\lambda/2$ ratio may be realized with our new pressed Ge monochromators.

b. LOW-TEMPERATURE TRANSFORMATIONS —ELASTIC-CONSTANT STUDIES (E. S. FISHER)

In a 1961 publication⁽¹⁴²⁾ the evidence was presented for a phase transition in α -uranium at some temperature between 41° and 43°K. The greatest effect of the transition was in the single crystal elastic moduli, where the data were obtained for c_{11} to 4°K and for c_{22} , c_{33} and c_{44} to 30°K. Measurements of the remaining 5 elastic moduli at temperatures below 44°K and of c_{22} , c_{33} and c_{44} below 30°K were prevented by breakage of the cements that were used to couple the ultrasonic waves to the single crystals. During the past year we have found that a coupling cement made with Dow Corning Silicone high-vacuum grease can be cooled by an appropriate technique so that the stresses produced by anisotropic thermal expansion of a metal single crystal do not fracture the acoustic bond. This discovery has enabled the completion of measurements of the 9 elastic moduli in the temperature range of 44° to 4°K.

Results: The results of this study are quite surprising and present a problem that is seemingly more complex than the 43°K transition, hereafter referred to as the upper transition. The complex nature of the results is best illustrated by the plot of c_{11} vs temperature given in Figure 184. The precipitous decrease in

* Resident Research Associate from Washington State University, Pullman, Washington.

⁽¹⁴¹⁾ Annual Report for 1964, Metallurgy Division, ANL-7000, p. 161.

⁽¹⁴²⁾ Fisher, E. S., and McSkimin, H. J., Phys. Rev. **124**, 67 (1961).

46218

FIG. 184. Temperature Dependence of Compressional Mode Stiffness Moduli, c_{11} , ρV_D^2 and ρV_F^2 for α -uranium.

c_{11} (as determined from measurements of compressional wave velocities propagated in the [100] direction) upon cooling to the upper transformation is shown in the right side.

Between 46° and 38°K attenuation of the acoustic waves prevented accurate measurements. It is clear, however, that c_{11} decreases from a maximum value of 2.15 dynes/cm² at 250°K to a minimum value that is less than 0.8 dynes/cm². Upon further cooling c_{11} increases as shown by the curve with arrows pointing towards the left of the figure. There is a slight minimum at 20°K and a smooth curve between 16° and 2°K. Upon heating from 2°K the curve is reproduced only up to approximately 10.5°K at which point the heating curve deviates from the cooling curve. The heating curve shows no fine structure between 2° and 22.5°K, at which point c_{11} begins to increase rapidly with temperature up to 25°K and then decrease smoothly upon further heating. The two curves coincide at 35° ± 1°K.

These solid lines are perfectly reproducible if the heating and cooling cycles start at 10.5° and 35°K, respectively. When, however, the temperature cycles begin at intermediate points, the measurements fall along lines that are schematically represented by the dashed lines connecting the solid lines. That is, the data points fall along a curve that is parallel to that part of the solid heating curve between 10.5° and 22.5°K.

The character of the solid lines suggests that the

mechanism of the transition requires under-cooling and over-heating, as in the case of typical hysteresis curves. One might then suspect that the transition point on cooling is either 18° or 16°K. The intermediate cycle data show, however, that the transition occurs at some temperature that is slightly higher than 35°K. That is, there exists a deviation between heating and cooling curves if the cooling cycle is stopped at any temperature less than 35°K. The effect of the transition increases with decreasing temperature, with the maximum effect at 10.5°K and below.

The intermediate cycle curves suggest also that another "critical" temperature exists between 21° and 22°K. That is, when the crystal is cooled to below this critical temperature the heating curve undergoes a slope inversion at the intersection with the full cycle heating curve. This slope inversion occurs at 22.5°K after the crystal is cooled below 10.5°K. The slope inversion temperature increases from 22.5° to 25°K as the minimum cooling temperature is increased.

As in the case of the upper transition the effects of the lower transitions are markedly anisotropic. The c_{22} modulus (from compressional waves in the [010] direction) is apparently not affected at all by the transitions. This is shown in the basic data plots of Figure 185, where the fractional changes in the frequency for a resonance condition are plotted against temperature for several compressional wave modes. The reference frequencies are those at 77°K and the change in frequency corresponds to the change in wave velocity when the changes in crystal dimensions are neglected. In all of the plots the dots correspond to data obtained during the full cooling cycle and the circles (with centered dots) are the heating cycle data points. For c_{22} the upper transition occurs sharply at 40.5°K and total change in frequency during cooling to 2°K is only 1%, in contrast to the >10% change in frequency for the c_{11} mode. The difference between heating and cooling points is extremely slight and there appears to be a very small change in slope upon heating through 22.5°K. The latter effect could be the result of a slight error of ±¼° in orienting the wave propagation direction.

The c_{33} data (Figure 185) do, however, show significant effects of the lower transitions, with the upper transition indicated at 41.5°K. In this case a significant change in slope occurs at approximately 38°K during the heating and cooling cycles. The cooling-cycle data show no further significant deviations from a smooth curve. The heating data show a well defined change in slope at 22.5°K.

The data shown in the bottom two sections of Figure 185 are from longitudinal waves propagated in two different intermediate directions, E_{qL} deviating 35.5°

from [001] in the (100) plane and D'_{QL} deviating only 8.2° from [001] in the (010) plane. Both sets of data show the slope change at 38°K that was observed in the c_{33} data. E_{QL} shows, in addition, the deviation between heating and cooling data at 35°K . The D'_{QL} data shows several additional points of interest: (1) the upper transition involves a minimum at 43°K and a sudden shift at 41°K , (2) an abrupt change in slope at 22.5°K on cooling as well as heating and (3) a well-defined reversal in slope of the cooling curve at 18°K .

Alpha-uranium has three independent shear moduli, c_{44} , c_{55} and c_{66} . The latter two moduli relate the stress to shearing of (100) planes relative to each other, c_{55} corresponding to a shear in the [001] direction and c_{66} to the [010] direction. The c_{44} shear distorts the (100) plane. The lower transitions have a relatively small effect on c_{44} , as shown by the basic data given in Figure 186. c_{55} and c_{66} are, however, grossly affected in magnitude and also in the attenuation of the wave modes producing the corresponding shear displacement. The velocity of pure c_{55} mode could not be measured at any temperature below 44°K . The c_{55} measurements given in Figure 187 were necessarily obtained indirectly from measurements of the effect of a c_{55} component on a transverse wave mode containing c_{44} displacements.

5016

FIG. 185. Temperature Variation of Basic Data for Compressional Modes c_{22} , c_{33} , ρV_E^2 and ρV_D^2 , in α -uranium. Dots (·) are points obtained during cooling of sample; circles (○) are obtained during sample heating.

45017

FIG. 186. Basic Data for Variation of Shear Mode Stiffnesses with Temperature of α -uranium. Dots (·) are data points obtained during sample cooling and circles (○) are obtained during heating.

An example of this effect is given in the lower part of Figure 186. The values of c_{55} computed from such measurements are subject to considerably greater error than direct measurements, primarily because of the uncertainty in the values of c_{44} at temperatures where sudden changes occur. At temperatures below 18°K c_{55} should be accurate to within 1%, because c_{44} is relatively independent of temperature in this range. The latter data show that c_{55} decreases by at least 25% upon heating between 4° and temperatures in the range of $20 \pm 3^\circ\text{K}$. It appears that the minimum value occurs at 22.5°K . Upon further heating there is a sharp increase to a maximum at 28°K and, again, a sharp decrease at the upper transition. For c_{66} , direct measurements could be made between 36° and 22°K . The values of c_{66} below 22°K , Figure 188, were obtained from the data plotted in the center part of Figure 186. The results follow the c_{55} temperature very closely. Both c_{55} and c_{66} have considerable temperature dependence at 4°K and decrease by $>25\%$ on heating to the $20 \pm 3^\circ\text{K}$ range. Both have a pronounced maximum between the upper transition and 22.5°K , with the c_{66} peak at 35°K .

Because of the uncertainties in c_{55} and c_{66} at temperatures below 22°K and the attenuation of waves propagated at 45° to the a_0 axis, the values of c_{13} and c_{12} determined from existing data at temperatures in the range of 10° to 23°K are subject to very large errors. Consequently, it is unreasonable to even attempt to compute the linear compressibilities, β_{100} , β_{010} and

β_{001} in this temperature range. At 4°K, however, the errors in c_{13} and c_{12} are probably less than 5% and compressibility values are therefore probably accurate to within 3%. The compressibility values computed on this basis are plotted in Figure 189, with the dashed lines indicating where the values are uncertain to greater than 3%. At temperatures above 23°K the hysteresis in the c_{ij} has no significant effect on β_{010} and β_{001} . The c_{11} hysteresis is reflected in β_{100} where the cooling data indicate that no significant peak occurs at 22.5°K and that β_{100} may be almost constant between 4° and 23°K. The heating data, however, indicate a pronounced peak at 22.5°K, as would be expected for a phase transition. A very small peak is indicated in β_{010} at 22.5°K, whereas β_{001} undergoes a significant dip. These data indicate that the volume compressibility, β_v , passes through a dip on cooling and a peak on heating at 22.5°K.

46221

FIG. 187. Variation of c_{55} Shear Modulus with Temperature in the Region of Phase Transitions. Filled triangles (▲) represent heating data and open triangles (△) represent cooling data from crystal F' . Circles represent data subject to lesser errors.

46217

FIG. 188. Variation of c_{66} with Temperature in Region of Phase Transitions. Filled squares (■) and open squares (□) represent heating and cooling data, respectively, from crystal D' . Circles represent data subject to lesser errors.

The net effect of the transitions on the anisotropy of compressibility is quite pronounced. Whereas at 100°K β_{100} is only about twice β_{001} this ratio increases abruptly at the upper transition and β_{100}/β_{001} is approximately 5.4 at 4°K. About $\frac{2}{3}$ of β_v at 4°K is due to β_{100} whereas at 300°K β_{100} is less than $\frac{1}{2}$ of β_v .

Correlation with Thermal Expansion: Barrett et al.⁽¹⁴³⁾ have reported that the lattice constants a_0 and b_0 of α -uranium expand during cooling from 43° to 20°K and indicate that the linear expansion coefficients for all three lattice constants are near zero in the 4° to 20°K range. The possibility of a hysteresis in thermal expansion was not considered and Barrett's X-ray data are not sufficient to judge whether the lattice constants do vary between heating and cooling cycles. Experiments to investigate this possibility have recently begun at the Bell Telephone Laboratories, Murray Hill, New Jersey. The expansivities in all three crystal directions are being measured by K. Andres with the three-terminal, capacitor technique of G. K. White.⁽¹⁴⁴⁾ The samples are the same single

⁽¹⁴³⁾ Barrett, C. S., Mueller, M. H., and Hitterman, R. L., *Phys. Rev.* **129**, 625 (1963).

⁽¹⁴⁴⁾ White, G. K., *Nature* **187**, 927 (1960).

crystals that were used in the c_{11} and c_{33} measurements described above. At the time of writing, the data available show that the expansivity in the [010] direction between 12° and 19°K is clearly dependent on the rate of cooling. Fast cooling from 40° to 4°K shows that expansion does in fact occur over the whole range. Slow warming reproduces the cooling data up to $12 \pm 1^\circ\text{K}$, but further heating causes further expansion up to 19°K. Temperature cycling between 12° and 19°K causes a continuous increase in length and is indicative that a hysteresis in thermal expansion of the [010] direction does exist.

Correlation with Electrical Resistivity Measurements: During the past year there have been several reports, from two laboratories in France,^(145,146,147) on the effects of quenching and/or electron or neutron irradiation on the annealing out of excess resistivity produced by these two processes. Jousset⁽¹⁴⁵⁾ quenched uranium wires from 77° to 4°K and found that the 4°K resistivity is increased over that measured after slow cooling. This excess resistance at 4°K is gradually reduced by pulse annealing to temperatures above 4°K and is almost completely lost after a 22.5°K anneal in wires that were α -rolled and annealed or in pseudo-single crystals prepared by the $\beta \rightarrow \alpha$ treatment. Pulse annealing at higher temperatures than 22.5°K causes a re-introduction of the excess resistivity. There also exists a time dependence of the resistance at the pulse anneal temperature; for temperatures below 22.5°K the resistance decreases rapidly with holding time, whereas, at higher temperatures the resistance first increases before decreasing.

These observations are essentially the same as observed after electron⁽¹⁴⁶⁾ or neutron⁽¹⁴⁷⁾ irradiation at temperatures below 10°K. An extra resistance is re-introduced by pulse annealing at temperatures above a critical temperature, which varies from 20° to 35°K depending on the fabrication and high temperature annealing history, i.e., apparently depending on the preferred orientations within the polycrystalline wires.

Arajs and Colvin⁽¹⁴⁸⁾ found a somewhat similar effect in a study of the temperature dependence of resistivity in several different uranium samples. Samples cooled to 4°K and slowly heated to 80°K contained an extra resistance that annealed out within a few hours.

Correlation with Hall Coefficient: The Hall coefficient

46215

FIG. 189. Temperature Dependence of Linear and Volume Compressibilities of α -uranium. Dashed lines indicate uncertainties in data causing errors of greater than 3%. Arrows indicate heating ($\rightarrow$) and cooling ($\leftarrow$) cycles.

coefficient (R) measurements by Berlincourt⁽¹⁴⁹⁾ were actually the earliest data pointing to a phase transition in the region of 20°K. In two polycrystalline rods, one reactor grade and one high purity, R was essentially temperature independent between 18° and 4°K and increased markedly upon heating to 41°K. The increment between 19° and 41°K was considerably greater in the high purity rod and in fact showed a change in algebraic sign at 20°K.

Correlation with Specific Heat: The heat capacity of α -uranium has been measured with a high degree of accuracy at intervals of 2°K in the range of 4° to 300°K.^(150,151) These data give no indication of a first or second order phase transition occurring in this temperature range. Perhaps heat capacity measurements at very small temperature intervals will permit a detection of the heat capacity peaks associated with the several transformations. There is, however, the possibility that the close proximity and anisotropy of the

⁽¹⁴⁵⁾ Jousset, J. C., Acta Met. **14**, 193 (1966).

⁽¹⁴⁶⁾ Lucasson, P., Lucasson, A., and Jousset, J. C., Phys. Lett. **12**, 4 (1964).

⁽¹⁴⁷⁾ Burger, G., Isebeck, K., Jousset, J. C., and Quere, Y., Phil. Mag. **11**, 621 (1965).

⁽¹⁴⁸⁾ Arajs, S., and Colvin, R. V., J. Less-Common Met. **7**, 54 (1964).

⁽¹⁴⁹⁾ Berlincourt, F. G., Phys. Rev. **114**, 969 (1959).

⁽¹⁵⁰⁾ Flotow, H., and Lohr, H. R., Phil. Trans. Royal Soc. (London) A**247**, 55 (1955).

⁽¹⁵¹⁾ Flotow, H., and Osborne, D. W., Phys. Rev. **151**, 564 (1966).

upper and lower transitions causes a smearing of the peaks so that one has, in effect, an extra contribution to the heat capacity at all temperatures below 43°K. This could possibly account for the large deviation between the Debye temperatures computed from heat capacity data, θ_s , and that computed from the 4°K elastic moduli, θ_e . The highest θ_s reported is that of Flotow and Osborne,⁽¹⁵¹⁾ 222°K, whereas θ_e computed from our present data is 252.7°K. Since $\theta_s = \theta_e$ at 0°K, according to theory, and agreement is quite good (within 5°K) for most metals at 4°K, the large deviation for uranium could arise from the extra contributions to C_p from the phase transitions.

Correlation with Superconductivity: The temperature and pressure at which pure α -uranium transforms to a bulk superconductor has received considerable attention during the past year.^(152,153,154) Magnetic induction measurements with single crystals indicate that a relatively sharp transition occurs between 0.21° to 0.25°K.⁽¹⁵⁴⁾ Heat capacity measurements show, however, that α -uranium is not a bulk superconductor at zero excess pressure, but the superconducting state is produced by the application of hydrostatic pressure.⁽¹⁵³⁾ It is, then, concluded that the superconducting properties detected at zero pressure are due to a connected network of superconducting filaments. These filaments are evidently associated with strains that are produced before the sample reaches the temperatures of the measurements. These strains are not entirely due to the anisotropy of thermal expansion, since single crystals exhibit a sharp transition. It appears that the atomic movements produced during the phase transitions at <40°K may be responsible for the superconducting transitions occurring near 0.2°K, whereas the superconductivity observed at higher temperatures is due to strains derived from other sources. On this basis filamentary superconductivity will always be observed in α -uranium single crystals unless the strains produced by cooling from 40°K can be erased by extremely slow cooling.

Conclusions: The temperature of the upper transition of α -uranium is anisotropic and occurs in the range of 40.5° to 43°K; no significant hysteresis is found for a given crystal direction. This transition probably involves an abrupt change in the states of the 5f electrons, from the conduction band to partially localized states, as suggested by Zachariasen.⁽¹⁵²⁾

The transitions below 40.5°K appear to be associated with structural changes that require greater driving energies than are needed for electronic changes.

⁽¹⁵²⁾ Geballe, T. H., Matthias, B. T., Andres, K., Fisher, E. S., Smith, T. F., Zachariasen, W. H., *Science* **152**, 755 (1966).

⁽¹⁵³⁾ Phillips, N. E., Ho, J. C., and Smith, T. F., *Phys. Rev. Letters* **17**, 694 (1966).

⁽¹⁵⁴⁾ Gardner, W. E., and Smith, T. F., To be published.

The hysteresis in the elastic moduli and thermal expansion and the time dependence of the annealing out of excess electrical resistance appear to be manifestations of atomic movements that occur during the transitions below 38°K.

c. IRRADIATION GROWTH (B. LOOMIS)

The study of the growth or length change of uranium during thermal neutron irradiation was continued in this report period. Length changes of uranium crystals were continuously determined during irradiation at temperatures between 5°K and 550°K. The apparatus used in this study was previously described in pages 235 to 237 of ANL-7000.

The elongation of a uranium single crystal in the [010] direction during irradiation is shown in Figure 190 where the instantaneous length change $\ln L/L_0$ and the growth coefficient G are plotted against the fraction of atoms fissioned. The growth coefficient G is defined as the ratio of the instantaneous length change and the fraction of atoms fissioned. After an initial period of low growth, during the 20°K irradiation, the single crystal elongated with a constant G that was substantially reduced on increasing the irradiation temperature. The length changes of pseudo-single crystals, i.e., crystals with substructure, in the [100], [010], and [001] directions on irradiation at 20°K are shown in Figure 191 where it can be seen that the rate of elongation in the [010] direction is approximately twice the rate of contraction in the [100] direction. The rate of elongation in the [010] direction of the pseudo-single crystal was significantly less than in the single crystal although both types of crystals exhibited similar growth behavior. The elongation of a polycrystalline specimen with a highly preferred [010] orientation of the grains resulting from swaging and recrystallizing at 475°C is shown in Figure 192. The growth coefficient for a polycrystalline specimen is expected to be less than the coefficient for [010] oriented single crystals since some of the grains in the polycrystalline specimen are not aligned in the [010] direction. Nevertheless a tentative evaluation of this misorientation effect has shown that the growth coefficient of polycrystalline specimens is approximately 1/4 of the growth coefficient for single crystals at 10°K. The polycrystalline specimen had a growth behavior different from that of the single crystals in that a maximum G was observed before the onset of constant growth.

A preliminary evaluation of data obtained during irradiation of crystals at temperatures above 70° indicates that uranium crystals have a minimum, approximately constant, growth coefficient between 125° and 500°K, and that the growth coefficient increases slightly at about 50°K. The temperature dependence

FIG. 190. Irradiation Growth of a Uranium Single Crystal in the [010] Direction.

FIG. 191. Irradiation Growth of Uranium Pseudo-Single Crystals in the [100], [010] and [001] Directions.

45944

of irradiation growth between 5°K and 550°K is shown in Figure 193.

Irradiation of the crystals was interrupted as indicated in Figure 190 and Figure 192 to study the re-

covery of the irradiation-induced length changes. The annealing behavior of the irradiated crystals is shown in Figure 194 where each data point represents the accumulated length change that resulted from anneal-

Fig. 192. Irradiation Growth of Polycrystalline Uranium at 10°K.

Fig. 193. Temperature Dependence of Irradiation Growth in Uranium Single Crystal and Polycrystalline Material.

ing a specimen one hour at the indicated temperature. After each pulse anneal the specimen was cooled to 4.3°K to determine the amount of recovery. Approximately 16% of the growth of the polycrystalline specimen was recovered by annealing to 480°K, whereas essentially no recovery of the elongation was affected in the crystal with the [010] orientation and less than 7% of the contraction in the [100] oriented crystal was recovered. The magnitude of recovery in these specimens stands in the inverse order of the magnitude of their growth coefficient, i.e., the polycrystalline specimen underwent the largest amount of recovery and had the smallest growth coefficient. The polycrystalline specimen as well as the single crystals elongated on annealing at temperatures up to approximately 40°K (Figure 194). At ~100°K a recovery

stage was quite evident for the [010] and [100] oriented crystals with no further significant recovery until an annealing temperature of 525°K was reached where both crystals elongated. In the polycrystalline specimen substantial recovery of the irradiation-induced elongation commenced at ~125°K.

Several mechanisms have been proposed to explain irradiation growth.⁽¹⁵⁵⁻¹⁵⁸⁾ The results of this study

⁽¹⁵⁵⁾ Buckley, S. N., *Properties of Reactor Materials and the Effects of Radiation Damage* (Butterworth's, London: 1962), p. 143.

⁽¹⁵⁶⁾ Seigle, L. L., and Opinsky, A. J., *Mechanism of Dimensional Instability of Uranium*, Nucl. Sci. Eng. **2**, 38-48 (1957).

⁽¹⁵⁷⁾ Pugh, S. F., *The Growth of Alpha-Uranium Under Irradiation*, UKAEA Report AERE-M/R 873 (1952).

⁽¹⁵⁸⁾ Burke, J. E., and Turkalo, A. M., *Nuclear Science and Technology Extracts from Reactor Science and Technology* (4), pp. 127-137, USAEC Report TID-2505 (1954).

Fig. 194. Recovery of Irradiation-induced Length Changes in Uranium Crystals.

46103

seem to uniquely suggest that elongation in the [010] direction results from the internal precipitation of planar clusters of interstitial atoms that create extra planes and contraction in the [100] direction results from planar clusters of vacancies eroding planes. The following results of the present study and the results of other investigators support this mechanism:

1. The enhanced growth of uranium crystals at irradiation temperatures below 100°K clearly precludes any theory of growth embodying long-range thermal diffusion.⁽¹⁵⁶⁾
2. For the irradiation dose received in these low temperature experiments the uranium crystals underwent dimensional distortion at a constant rate. It has been reported⁽¹⁵⁹⁾ that irradiation growth continues undiminished even after 0.4% of the atoms have been fissioned and therefore irradiation growth appears to be unlimited. Since complete twinning of a uranium crystal gives only about 20% elongation, it must be concluded that localized lattice rotation^(157,158) does not contribute significantly to the growth process.
3. The lack of any significant annealing of the irradiated single crystals and their subsequent growth behavior (Figure 191) shows that the major effect of irradiation at low temperatures is to produce a change in shape.
4. The onset of a constant growth or contraction

rate (Figures 190, 191, and 192) may be construed to indicate a steady state condition in which the creation of new defect clusters is balanced by radiation annealing and thermally activated annealing of defects.

5. Planar clusters of point defects have been observed in irradiated uranium by transmission electron microscopy.⁽¹⁶⁰⁾
6. The dimensions of the uranium unit cell are only slightly affected by neutron exposures of 2.6×10^{18} nvt.⁽¹⁶¹⁾

Since the elongation in the [010] oriented crystal (Figure 191) was approximately twice the contraction of the [100] oriented crystal during irradiation at 20°K and probably at lower temperatures as well, either the [100] direction was not the direction of maximum shrinkage or the vacancies did not cluster as readily as the interstitials. If the [100] direction was the direction of maximum shrinkage then the density of the crystals should have decreased on irradiation. The precision of the density measurements thus far have not allowed a determination of this point.

The annealing studies (Figure 194) have shown that

⁽¹⁶⁰⁾ Hudson, B., *The Crystallography and Burgers Vectors of Dislocation Loops in α -Uranium*, Phil. Mag. **8**, 949-960 (1964).

⁽¹⁶¹⁾ Cummings, W. V., Jr., *The Effects of Low Neutron Exposures at Low Temperatures on the Hardness and Tensile Properties of Natural Uranium*, USAEC Report HW-60326 (1959).

⁽¹⁵⁹⁾ Kittel, J. H., and Paine, S. H., *Effects of High Burnup on Natural Uranium*, USAEC Report ANL-5539 (1957).

irradiated uranium specimens, regardless of their orientation or perfection, elongate slightly on annealing at temperatures up to 40°K. This suggests that defects of an interstitial nature are mobile at temperatures below 40°K and can thus join existing clusters of interstitials producing elongation in the [010] direction or annihilate vacancies producing an elongation [100] direction. Electrical resistivity changes observed in annealing studies on polycrystalline uranium irradiated with neutrons⁽¹⁶²⁾ and electrons⁽¹⁶³⁾ as well as the annealing of quenched uranium⁽¹⁶⁴⁾ suggest that a defect of interstitial nature is mobile between 4°K and 20°K. In this study interstitial mobility during annealing of the irradiated specimens would not produce a substantial length change since only those interstitials that were not attached to the very stable defect clusters would be involved. However, it is not certain that interstitial mobility in itself during irradiation was responsible for the decreased growth rate on increasing the irradiation temperature from 5°K to 40°K as shown in Figure 193.

The recovery stage centered about 100°K (Figure 194) resulted in elongation in the [100] oriented crystal and contraction in the [010] oriented crystal between 40°K and approximately 125°K. These length changes indicate that vacancy as well as interstitial defects are mobile resulting in their annihilation. Therefore, the pronounced decrease of the growth rate between 40°K and 125°K (Figure 193) resulted from a substantial reduction in the formation of vacancy and interstitial clusters. The electrical resistivity changes observed on annealing neutron-irradiated uranium seem to show that vacancies migrate at temperatures below 100°K.⁽¹⁶²⁾

d. THE SINGLE CRYSTAL SUSCEPTIBILITY OF ALPHA FROM 2°K TO 300°K (J. W. ROSS AND D. J. LAM)

Measurements of the elastic constants⁽¹⁶⁵⁾ and neutron diffraction studies⁽¹⁶⁶⁾ on single crystals of α -uranium indicate that magnetic order may exist in this allotrope. In order to explain the unusual volume-temperature dependence around 50°K and the pres-

⁽¹⁶²⁾ Burger, G., Iseback, K., Wenzil, H., Jousset, J. C., and Quere, Y., (a) *Irradiation of Uranium with Neutrons at 4.5°K*, Phil. Mag. **11**, 621-625 (1965), (b) 10ème Colloque de Metallurgie, Saclay, June 1966.

⁽¹⁶³⁾ Jousset, J. C., Lucasson, A., and Lucasson, P., *Electron Irradiation of Uranium at 7°K*, Phil. Mag. **13**, 887-897 (1966).

⁽¹⁶⁴⁾ Jousset, J. C., *Annealing of Uranium Quenched from 100 to 4.2°K*, Acta Met. **14**, 193-200 (1966).

⁽¹⁶⁵⁾ Fisher, E. S., and McSkimin, H. J., Phys. Rev. **124**, 67 (1961).

⁽¹⁶⁶⁾ Barrett, C. S., Mueller, M. H., and Hitterman, R. L., Phys. Rev. **129**, 625 (1963).

44880

FIG. 195. Magnetic Susceptibility Differences of Single Crystal α -uranium.

sure dependence of the superconducting transition temperature, Geballe, et al.⁽¹⁶⁷⁾ have proposed a localization of the magnetic moment of the conduction electrons to the extent of $0.4 \mu_B$ per uranium atom below 50°K. Magnetic susceptibility measurements⁽¹⁶⁸⁾ on polycrystalline samples, however, show no evidence of this assumption. The measurements on single crystals reported here are more conclusive.

We determined the temperature dependence of the magnetic susceptibility for the polycrystalline α -uranium available by means of a microbalance technique and found it to be constant at $1.59 \pm 0.02 \times 10^{-6}$ emu gm⁻¹. The single-crystal paramagnetic anisotropy was measured with the self-compensating torque magnetometer described in ANL-7155. The susceptibility differences $\chi_a - \chi_b$, $\chi_c - \chi_b$ and $\chi_a - \chi_c$ were measured for a pseudo unit-cell single crystal and three other crystals with only two parallel faces perpendicular to a principal crystallographic direction.

The results for the pseudo unit cell are shown in Figure 195. Results on the other three crystals are in agreement with these values to within 3%. The largest difference, $\chi_a - \chi_b$, is only 12% of the average susceptibility and is relatively constant down 40°K. Below this temperature χ_b increases by 2%. The unusual behavior of $\chi_a - \chi_c$ between 20°K and 40°K, although small, is real and consistent for both the pseudo unit cell and the other appropriate single crystal.

Our work does not indicate magnetic order below 300°K and certainly excludes any magnetic tran-

⁽¹⁶⁷⁾ Geballe, T. H., Matthias, B. T., Andres, K., Fisher, E. S., Smith, T. F., and Zachariasen, W. H., Science, **152**, 755 (1966).

⁽¹⁶⁸⁾ See reference 16 of Geballe's paper.

formations below this temperature. From Geballe's localization assumption an increase in susceptibility of approximately 0.5×10^{-6} emu gm $^{-1}$ is expected on going from 40°K to 2°K. This was not observed in either the single crystal or polycrystal data. A nearly free electron model with about six electronic states per eV per atom would account for the measured susceptibility and its temperature dependence. On this model the small anisotropy in susceptibility indicates the Fermi surface is non-spherical. The small changes around 40°K presumably reflect the relative movement of the Brillouin zone boundaries with respect to the Fermi surface since it is here that the atomic volume-temperature curve changes sign.

Similar measurements are being made on single crystals of scandium metal to determine if it is an antiferromagnetic element as suggested by other single crystal susceptibility results.⁽¹⁶⁹⁾

e. EQUIATOMIC TERNARY COMPOUNDS OF URANIUM-ALUMINUM WITH GROUP-VIII TRANSITION ELEMENTS (D. J. LAM AND J. B. DARBY, JR.)

An investigation of the vertical section of the system $\text{UFe}_2\text{-UAl}_2$ has been completed. It was reported previously (ANL-6516) that two ternary phases existed in this system. A subsequent investigation of this system by Petzow and co-workers⁽¹⁷⁰⁾ indicated the existence of only one ternary phase with the C14-type structure. A more detailed investigation of this quasibinary system, especially in the composition and temperature range where the second ternary compound was reported to be stable, has been carried out in an attempt to resolve the discrepancy. The results of the present investigation are shown in Figure 196. The work has confirmed the earlier contention that two ternary phases exist in this quasibinary system. One phase, designated as $\text{U}(\text{AlFe})_2$, has the hexagonal C14-type structure with a variable composition range of stability, and the other phase is essentially an equiatomic ternary compound UAlFe , stable below 700°C. The latter phase has a hexagonal structure which has been established⁽¹⁷¹⁾ as the Fe_2P type (or C22 type). The results of an independent investigation⁽¹⁷¹⁾ indicate that many examples of this structure type exist.

Two additional examples of compounds isostructural

⁽¹⁶⁹⁾ Chechernikov, V. I., Pop, Iuliy, and Naumkin, O. P., J.E.T.P. **44**, 1228 (1963).

⁽¹⁷⁰⁾ Petzow, G., Steeb, S., and Tank, R., Z. Metall. **53**, 526 (1962).

⁽¹⁷¹⁾ Dwight, A. E., in this report.

44261

FIG. 196. The Phase Diagram of the Vertical Section $\text{UFe}_2\text{-UAl}_2$.

TABLE 75. LATTICE CONSTANTS OF THREE Fe_2P -TYPE COMPOUNDS

Alloy Composition	Heat Treatment		Lattice Parameters (Å)
	Temp. ^a (°C)	Time (Wk)	
UAlFe	675	2	$a_0 = 6.672 \pm 0.001$ $c_0 = 3.981 \pm 0.001$ $c/a = 0.597$
UAlCo	725	2	$a_0 = 6.686 \pm 0.001$ $c_0 = 3.966 \pm 0.001$ $c/a = 0.593$
UAlIr	1000	1	$a_0 = 6.968 \pm 0.001$ $c_0 = 4.030 \pm 0.001$ $c/a = 0.579$

^a Alloys were water quenched from the temperatures indicated.

tural with UFeAl were found in this investigation and these are the compounds UAlCo and UAlIr . The lattice constants of the three Fe_2P -type compounds are listed in Table 75. This work has been summarized in a paper that has been accepted for publication in the Journal of Nuclear Materials.

2. Plutonium

a. PREPARATION OF HIGH-PURITY METAL

(G. B. O'KEEFE, J. A. AMY, J. J. RECHTIEN, AND M. B. BRODSKY)

Electrorefining of plutonium metal in a fused-salt electrolyte was continued at a low rate. A gross weight of 1.25 kg of refined metal was obtained from 1.8 kg of impure anode stock. After cleaning and sampling the consolidation melts, a net of 0.99 kg of usable metal remained, which was added to the 0.60 kg of pure metal available at the start of the year. During 1966, other ANL divisions used 0.003 kg and programs of the Metallurgy Division consumed 1.1 kg.

Chemical and spectrographic analysis had been discontinued in 1965 in the interest of economy and because it was believed that the process variables were satisfactorily controlled. During the course of metallographic examination of electrorefined metal, which had been heated at high pressures and temperatures, appreciable amounts of inclusions were seen. A program of chemical and metallographic examination was initiated and it was concluded that much of the metal produced during 1966 was not as pure as had been obtained before the analyses were stopped. Close scrutiny of operating procedures did not reveal the definite sources of the impurities (primarily carbon, aluminum, chromium, iron, and nickel), and the latest metal produced has been of high quality, again. In view of this experience, a definite schedule of metallographic and chemical analyses is being instituted again.

The desirability of producing higher-purity plutonium metal has led to a continuation of the zone-refining investigations initiated last year. The commercial vertical zone-refining unit has been placed in a glovebox and experiments with 0.25 in. and 0.125 in. diameter plutonium rods have been conducted. The following difficulties were encountered: (1) welding of the plutonium rods, to initiate a floating zone, is difficult, probably owing to oxide film forming in the present vacuum system at about 10^{-5} torr, (2) holding the molten zone after its formation is a problem since the metal has a tendency to drip immediately after melting. Despite the above problems molten zones have been moved in the 0.125 in. diameter plutonium and this indicates the feasibility of the method although modifications in the equipment are necessary. Inasmuch as a better vacuum system is required to offset the high reactivity of the plutonium, a commercial system with capability in the low 10^{-8} torr range will be purchased soon.

The difficulty in holding the molten zone might be corrected by constructing finer controls on the elec-

tron-beam system or by going to a crucible-container horizontal system. The difficulty in the latter approach is possible contamination of the plutonium by the crucible used to contain it. This method has been studied by melting the plutonium in a water-cooled copper boat with induction melting equipment already available. While successful melting has been obtained, the poor vacuum and subsequent oxide formation on the plutonium has hindered attempts to determine whether the water cooling or levitation of the plutonium prevent contamination of the plutonium. Further experiments are in progress, and if it is demonstrated that the horizontal refining process does not cause crucible contamination, this process will be pursued preferentially.

b. ELECTRONIC STRUCTURE OF THE ALPHA PHASE (M. B. BRODSKY)

The search for magnetic order in alpha plutonium and to a lesser extent in delta plutonium has been the cause of much effort. The status of this effort was explored extensively last year at the Third International Conference on Plutonium Metallurgy,^(172,173) with the result still in doubt. Measurements, made during the past year, of the transverse magnetoresistivity of rolled alpha plutonium constitute strong evidence for the existence of a magnetic transition.

Figure 197 shows the effect of applied field on the potential, which is proportional to resistivity, measured perpendicular to the rolling direction at 6°K. The resistivity increases with very small fields, decreases to a minimum near two to three kilogauss, and then increases with field. The potential at 6°K measured parallel to the rolling direction, Figure 198, is similar. Results obtained at 13°K are plotted in Figure 199 and are typical of data for 21° and 25°K. No significant minimum exists in these curves except for a decreasing field. Preferred orientation in the samples has had little effect on the results.

Some of the detailed behavior of the magnetoresistivity shown at the higher temperature should be considered with caution since the resistivity of plutonium changes considerably with temperature above 10°K. An additional source of uncertainty is the effect of self-damage on the electrical resistivity. The self-damage caused an increase of about 0.01 μ v/min in these experiments, and it was necessary to separate the

⁽¹⁷²⁾ Lallement, R., and Solente, P., "Physical Properties Alpha Plutonium and Delta-Phase Alloys at Low Temperatures" *Plutonium 1965*, pp. 147-161, Chapman and Hall, London (1967).

⁽¹⁷³⁾ Friedel, J., "Report on Papers in Session II-A", *loc. cit.*

45566
Fig. 197. Resistive Potential of Alpha Plutonium vs Magnetic Field at 6°K (Measured Perpendicular to the Rolling Direction)

45565
Fig. 198. Resistive Potential of Alpha Plutonium vs Magnetic Field at 6°K (Measured Parallel to the Rolling Direction).

effect of self-damage from the effects of the magnetic field. The hysteresis between successive cycles may be due to a systematic error in the correction for self-damage. At any rate, the decrease in resistivity with applied field, as shown in Figures 197 and 198, is definitely larger than any such errors.

In general, the magnetoresistivity of a metal is

positive, i.e., the resistivity increases with magnetic field.⁽¹⁷⁴⁾ The only special cases known in which negative magnetoresistivities are produced involve ferromagnetic metals and alloys, or thin ultra-pure specimens, where the mean free paths of the electrons are

⁽¹⁷⁴⁾ Ziman, J. M., "Electrons and Phonons", Oxford University Press, London (1960), pp. 490-495.

45567

FIG. 199. Resistive Potential of Alpha Plutonium vs Magnetic Field at 13°K (Measured Perpendicular to the Rolling Direction).

45996

FIG. 200. Magnetic Susceptibility of Plutonium (Plotted as Weight Change) vs Temperature. Room temperature data correspond to $X = 2.15 \times 10^{-6}$ emu/g (filled circles represent the weight change between zero and 14.5 kilogauss, and the open circles are for the weight change between 4.0 and 14.5 kilogauss).

long compared to the sample dimensions. Although samples of high-purity plutonium were used, the large residual resistivity, $16 \mu\text{-ohm-cm}$, demonstrates that the samples were not ultra-pure. The negative magnetoresistivity in alpha plutonium, accordingly, must be due to magnetic effects. The negative magnetoresistivity is generally associated with the rotation of domains. Measurements have also been made at 54° and 78°K , but the low-field magnetoresistivities at these temperatures are small compared to the experimental uncertainties and it is not clear that there is a minimum in these curves. Therefore, the data do not establish the maximum temperature of the effect, viz., the Néel temperature.

The above presentation seems so straightforward that it might be expected that more direct measurements of magnetic order should show large effects. That such is not the case is seen in Figure 200, where the weight change in a gradient magnetic field (proportional to the magnetic susceptibility) has been plotted against temperature for alpha and delta plutonium. These data do not have maxima, as is usually the case for antiferromagnetism, nor do they rise to extremely high values, as is the case for ferromagnetism. If the rise in susceptibility below 40°K corresponds to the onset of some magnetic order, then only a very small fraction of a Bohr magneton could be involved per atom. It would seem reasonable, therefore, to think in terms of a magnetic order which the net moment is small because of opposing alignments of the individual spins. The detailed micro-

scopic nature of this antiferromagnetism cannot be solved without suitable neutron diffraction results.

It may be that susceptibility measurements on single crystals may show the more classical effects and therefore give better clues to the mechanism for the magnetism. Efforts in that direction will be attempted with single crystals, when they become available from the high-pressure techniques currently under study.

c. EFFECTS OF PRESSURE ON TRANSFORMATIONS (R. G. LIPTAI, R. J. FRIDDLE, AND L. T. LLOYD)

Publications

- R. G. Liptai, L. T. Lloyd, and R. J. Friddle, "Effects of High Pressure and Temperature on the Microstructure of Plutonium", *Bull. IMD-AIME* **1**, 35 (1966). Abstract
- L. T. Lloyd, R. G. Liptai, and R. J. Friddle, "Effects of Phase Transformations at High Pressures and Temperatures on the Microstructure of Alpha Uranium", *ibid.* Abstract.
- R. J. Friddle, R. G. Liptai, and L. T. Lloyd, "On the Use of Alkali Metals for Pressure Transmission in High-Pressure Investigation", *ibid.* Abstract.
- R. G. Liptai and R. J. Friddle, "The Phase Diagram of Plutonium at Pressures up to 75 kbar", *J. Less-Common Met.* **10**, 292-294 (1966).
- L. T. Lloyd, R. G. Liptai, and R. J. Friddle, "The Effects of High Pressure and Temperature on the Microstructure of Alpha Uranium", *J. Nucl. Mat.* **19**, 173-180 (1966).
- R. J. Friddle, R. G. Liptai, and L. T. Lloyd, "The Use of Alkali Metals for Transmission of Hydrostatic Pressure", *Trans. AIME* **236**, 1090-1091 (1966). Letter
- R. G. Liptai and R. J. Friddle, "The Effects of High Pressure on the Alpha $\rightleftharpoons$ Beta Transformation in Plutonium", *J. Nucl. Mat.* **20**, 48-56 (1966).
- R. J. Friddle, R. G. Liptai, L. T. Lloyd, and M. D. Odie, "Metallographic and X-Ray Studies of Alpha Plutonium", pp. 185-199, in *Technical Papers of the Twentieth Metallographic Conference*, RFP-658, The Dow Chemical Company, Golden, Colorado (October 1966).

The objective of this program is to study the effects of high pressure and temperature on transformations in actinide elements. Most of the effort during the past year has been directed towards the goal of developing techniques for preparing large crystals of plutonium and plutonium alloys in order to provide samples for use in studies of properties as a function of crys-

45524 Polarized Light 25X
FIG. 201. Composite Photomicrograph of a Plutonium Sample Pressurized to 57 kbar in Boron Nitride, Heated to the Liquid Phase and Cooled through the Liquid $\rightarrow$ Beta and Beta $\rightarrow$ Alpha Transformations at 50°C/hr.

tallographic direction. Experiments in the piston-cylinder high-pressure apparatus have shown that the main problem remaining is the elimination of the substructure in the alpha grains of plutonium. It was noted in last year's Annual Report (ANL-7155) that the substructure is probably due to one or both of the following factors; (1) the volume change during the beta $\rightarrow$ alpha transformation and (2) the pressure transmission by a solid medium.

A belt-type, high-pressure apparatus was purchased and adapted for use with plutonium to achieve a greater probability of successful runs at 54 kbar, the pressure for a zero volume change during the beta $\rightarrow$ alpha transformation.

The microstructure of plutonium cooled from the liquid phase at pressures between 50 and 60 kbar has revealed several interesting characteristics (Figure 201). Back-reflection Laue photographs and metallographic examinations demonstrate that the grains are large, but are composed of subgrains with low-angle boundaries. It appears that the plutonium sample is deformed plastically during cooling at high pressure. The strains resulting from plastic deformation are relieved by the formation of subgrains, a process that may be broadly classified as polygonization. This situation is similar to that of uranium. Several causes of the plastic deformation seem likely, namely, (a) non-hydrostatic components (shear stresses) of pressure produced in the high-pressure apparatus by the solid pressure-transmitting medium (boron nitride), (b)

anisotropy of thermal expansion and/or linear compressibility, and (c) transformation stresses.

The first condition can be reduced by surrounding the sample with an annulus of an alkali metal inside a tantalum capsule, providing truly hydrostatic pressures at elevated temperatures. This technique is presented in two of the publications listed above. Large beta and alpha grain size will tend to minimize the second condition. Conducting the experiments at pressures of 54 kbar should minimize the transformation stresses since the volume change between the beta

45504 8X
FIG. 202. Plutonium Sample Contained in Liquid Lithium While Heated to the Liquid Phase at a Pressure of 58 kbar.

45501 Polarized Light 50X
FIG. 203. Microstructure of Plutonium Sample after High Pressure and Temperature Treatments in Liquid Lithium. Sample was pressurized to 55 kbar, heated to 450°C (beta), held for 48 hours, and cooled at 40°C/hr through the beta → alpha transformation.

and alpha phases is zero but, apparently it is very difficult to achieve zero volume change exactly.

Two experiments are suggested with samples surrounded by an annulus of an alkali metal; (1) growth from the melt (liquid → beta → alpha) and (2) solid state growth (beta → alpha). Both experiments are designed to produce large beta grains free of strain. Figure 202 shows the result of containing liquid plutonium in liquid lithium at high pressures. The plutonium samples remained intact in only about 30% of the experiments. It appears that the previously oxidized sample surface serves as a container for the liquid plutonium, and the nature of the oxide is an important factor in containing the liquid sample in a liquid pressure-transmitting medium. The microstructure of the sample in Figure 202 showed the metal was free of microcracks and inclusions; however, no large improvement in grain size was realized.

The phase-transformation technique, where samples are surrounded by an alkali metal and only heated into the beta phase, has been the most promising. Metallography of a sample given this treatment is shown in Figure 203. Back-reflection Laue patterns (Figure 204a) demonstrated the sample is composed of essentially two grains although sub-graining is still present. Figures 204b and 204c are patterns of the two orientations obtained with smaller collimators. Evaluation of the phase transformation technique for growth of large plutonium crystals will continue.

Plutonium Alloys: The use of high-pressure techniques to grow large crystals of beta and delta plutonium has been investigated. It has been reported that increasing additions of titanium up to 1.05 atomic percent progressively shift the $\beta \rightarrow \alpha$ TTT curves to longer transformation times.⁽¹⁷⁵⁾ Gallium additions between 2 and 8 atomic percent retain delta plutonium at room temperature.⁽¹⁷⁶⁾ It was conjectured that additions of these elements in combination with the use of high pressure and temperature could be used to grow large crystals of the beta and delta phases. The pressure-temperature phase diagrams of various Pu-Ga and Pu-Ti alloys have been determined and are given in Figures 205 and 206. These results show that high pressures can not be used to grow crystals of the beta or delta phases by direct transformation from the liquid phase.⁽¹⁷⁷⁾

⁽¹⁷⁵⁾ Davy, L. G. T. and White, J. S., "The Kinetics of the $\beta \rightarrow \alpha$ Transformation in Plutonium-Titanium Alloys", *J. Nucl. Mat.* **12**, 221-225 (1964).

⁽¹⁷⁶⁾ Ellinger, F. H., Land, C. C., and Struebing, V. O., "The Plutonium-Gallium System", *J. Nucl. Mat.* **12**, 226-231 (1964).

⁽¹⁷⁷⁾ Liptai, R. G., and Friddle, R. J., "The Effects of High Pressure on Some Plutonium Alloys", to be published, *J. Nucl. Mat.*

45528 25 mil collimator 1 hr exposure 45529 10 mil collimator 4 hr exposure 45530 10 mil collimator 4 hr exposure

FIG. 204 Back reflection Laue Photograms of the Specimen Shown in Fig. 203 Tungsten radiation 50 kv 20 ma 3 cm specimen to film distance

45030

FIG. 205 The Phase Diagram of Pu-Ga Alloy (3 atomic percent Ga)

45031

FIG. 206 The Phase Diagrams of Pu-Ti Alloys (1, 3 and 6 atomic percent Ti)

d. DEFORMATION MECHANISMS OF ALPHA PLUTONIUM (R. G. LIPFAT AND R. J. FRIDDLE)

The objective of this study is to establish the deformation systems of alpha plutonium. Preliminary information was obtained on a large grained sample deformed plastically until fracture. The sample was produced by cooling from the liquid phase in a boron nitride container under high pressure (see above). Two slip systems were observed with long and slightly

wavy slip lines (Figure 207). The one surface analysis for determining the loci of slip planes of one of the two slip systems revealed that the slip plane lies in the (21X) family of planes. The analysis for the other system indicated that the slip planes lie in the zone comprised of those planes on the great circle connecting (101) and (120).

Detailed studies along these lines are planned. A two surface analysis will be used and specimens will be prepared by high-pressure techniques.

45523 Bright Field

15½×

FIG. 207 Composite Photomicrograph of a Plutonium Sample that Was Deformed Plastically until Fracture. Sample was prepared by being pressurized to 55 kbar, heated to the liquid phase, cooled at 40°C/hr through the liquid $\rightarrow$ beta and beta $\rightarrow$ alpha transformations.

e. ANTEMORPHIC EFFECTS (J. J. RECHTIEN)

A program has been initiated to investigate and explain antemorphic effects in elemental metals. An antemorphic effect is one resulting from the dependence of the properties of an allotrope on the allotrope

from which it is formed. Such effects, which are of necessity metastable, can be quite large. In particular, the maximum elongation of β -plutonium has been found to vary more than an order of magnitude depending on whether the β -phase is formed from γ -plutonium or α -plutonium.^(178,179) Further, the persistence with time of this effect has been demonstrated by the hardness measurements of Ekbohm.⁽¹⁸⁰⁾

The program will initially incorporate mechanical testing and elevated-temperature X-ray studies on plutonium. An effort will be made to find other physical measurements that are influenced by the differences in structure. Other polymorphic metals will be investigated to determine whether antemorphic effects are general phenomena. Promising metals are uranium and neptunium in the actinide series, lanthanum in the rare earth series, and strontium in the alkaline earth series.

⁽¹⁷⁸⁾ Nelson, R. D., Bowman, F. E., Kissinger, H. E., and Mastel, B., HW-84281, 3.51.

⁽¹⁷⁹⁾ Bowman, F. E., private communication.

⁽¹⁸⁰⁾ Ekbohm, L., private communication.

3. Neptunium

a. ELECTRONIC STRUCTURE (M. B. BRODSKY)

Publication

M. B. Brodsky and N. J. Griffin, "Hall Effect and Electrical Resistivity of Neptunium and Americium", *Bull. Am. Phys. Soc.* **11**, 92 (1966). Abstract.

As part of a study of the electronic structure of neptunium, the Hall effect and electrical resistivity were reported in the above publication and in an earlier Annual Report (ANL-7000) for neptunium metal obtained from the Oak Ridge National Laboratory. Metallographic examination of this metal had shown the presence of many inclusions and it is now known that the metal contained large amounts of carbon (3.5 *a/o*) and oxygen (0.37 *a/o*). Measurements of the Hall coefficient had revealed a large temperature dependence of the Hall effect, and at temperatures below 254°K there was a hysteresis in the Hall potential with applied magnetic field. These effects are now thought to be due to the presence of NpC, which has an antiferromagnetic $\rightarrow$ ferromagnetic transition at 200°K (see Section 5, p. 225).

Further studies have been made on a metal sample prepared at Argonne. The metal was prepared by the reduction of NpO₂ with Zn-Mg alloy, followed by the

vaporization of the zinc and magnesium, and consolidation of the neptunium product by arc-melting. Less than one-half gram of neptunium metal has been prepared by this procedure, thus far, and chemical analyses have not been made yet because of the small amount of material available. The results are still preliminary without any analyses but are of sufficient interest to report here. The data are summarized below with other available results, and with suitable comments about the possible effects of impurities on the property measured.

Hall Effect: Figure 208 shows a plot of the Hall coefficient versus temperature for the two metal samples discussed above. It is seen that the temperature dependence of the data for the metal prepared here is much lower than that of the Oak Ridge material. The much smaller maximum, near 80°K for the ANL neptunium, may be due to oxygen impurity (see below). The higher temperature results for the two samples agreed within a factor of three and when considered by a two-band model yield essentially the same result, i.e., a band structure with a nearly full 7*s* band and 5*f* band containing slightly more than five electrons. The conclusion presented before (ANL-7000) that the higher-temperature data substantially represent the situation in pure neptunium still seems to be valid.

45997

FIG. 208. Hall Coefficient of Neptunium Metal vs Temperature.

Electrical Resistivity: The electrical resistivity of neptunium seems to be insensitive to the nonmetallic impurities encountered here. No anomaly in resistivity was found in the Oak Ridge neptunium at the 200°K Curie point of NpC although "breaks" in the resistivity-temperature curve at 273°K had been found at Harwell.⁽¹⁸¹⁾ Resistivity ratios ($\rho_{300^\circ}/\rho_{4^\circ}$) are of uncertain value in judging the purity of the metal used. There is a large drop in the resistivity of NpC near its Curie Temperature⁽¹⁸²⁾ so that the presence of NpC impurity in neptunium metal would also cause a large, though not necessarily discontinuous, decrease in resistivity near 200°K. The extra drop in resistivity due to NpC impurity would then lead to a high resistivity ratio. In fact, this was observed in the Oak Ridge metal, which gave a resistivity ratio of 52 and implied a higher purity than the Harwell ($\rho_{300^\circ}/\rho_{4^\circ} = 34$)⁽¹⁸¹⁾ or Los Alamos ($\rho_{300^\circ}/\rho_{4^\circ} = 8.2$)⁽¹⁸³⁾ neptunium. The material designated ANL neptunium, above, has a resistivity ratio of about 7 and it is hoped that chemical analysis will shed some light on the meaning of this ratio in neptunium.

Magnetic Susceptibility: Preliminary measurements of the magnetic susceptibility of the neptunium metal produced here show a rise from 2.78×10^{-6} emu/g at 300°K to a maximum value of 15.61×10^{-6} emu/g at 30°K. The temperature of the maximum is very close to that found for an antiferromagnetic transition in NpO₂ (see D. Lam's report, page 225). The maximum susceptibility found there, 30×10^{-6} emu/g, would imply that the neptunium "metal" contains about 50 %

NpO₂. Correlation of these results with chemical analysis is especially desired. At any rate, the "breaks" in susceptibility found at 230° and 95°K with Harwell metal,⁽¹⁸⁴⁾ have not been observed here, and are most likely due to impurities.

b. MÖSSBAUER STUDIES (M. KALVIUS*, B. DUNLAP*, S. RUBY**, D. COHEN***, AND M. B. BRODSKY)

Observation of the Mössbauer effect in Np²³⁷ with Am²⁴¹ sources has made it possible to consider the use of this tool to make a number of interesting studies.⁽¹⁸⁵⁾ Studies have been made with the source as americium metal, AmO₂, and various alloys of americium. Although the best source used thus far, Am-Th solid solution, still has a line-width 15 times natural line-width, the magnitude of the isomer shift is large with respect to the line width. Therefore, a study has begun of the isomer shift as a function of neptunium valence state. After this calibration of the isomer shift has been completed, it will be possible to determine the valence states in a number of neptunium alloys from their isomer shifts. This approach may then be correlated with other properties such as magnetic susceptibility, Hall effect, electrical resistivity, etc., in order to establish the behavior of the actinide metals as a function of electronic configuration.

Magnetic splitting has been observed in Np Al₂.^(186,187) A study of solid solutions of neptunium in plutonium will permit the determination of magnetism in the alpha plutonium structure (see section 2b). Additional studies of magnetic splitting may be possible by cooling the sources to various temperatures. If such magnetic effects can be found with Am-Pu sources, then the magnetism of the delta phase plutonium may be investigated also.

(184) Gardner, W. E., quoted by H. A. C. McKay, J. S. Nairn, and M. B. Waldron, "The Chemistry and Metallurgy of Neptunium", Proc. of the 2nd Intern. Conf. on Peaceful Uses of Atomic Energy, **28**, 299 (1958).

* Solid State Science Division

** Physics Division.

*** Chemistry Division.

(185) Stone, J. A., and Pillinger, W. L., "Recoilless Gamma-Ray Emission After Alpha Decay", Phys. Rev. Letters **13**, 220 (1964).

(186) Stone, J. A., and Pillinger, W. L., "Nuclear-Moment Ratios in Np²³⁷ from Mossbauer Spectra", Bull. Am. Phys. Soc. **11**, 471 (1966).

(187) Kalvius, M., Dunlap, B., Ruby, S., and Brodsky, M. B., "Temperature Dependence of the Hyperfine Field in NpAl₂ by the Mossbauer Effect in Np²³⁷", Bull. Am. Phys. Soc., in press

(181) Lee, J. A., Meaden, G. T., and Mendelssohn, K., Cryogenics **1**, 52 (1960).

(182) Brodsky, M. B., "Resistivity of NpC", unpublished data.

(183) Olsen, C. E. and Elliott, R. O., "Electrical Behavior of Plutonium-Neptunium Alloys", Phys. Rev. **139**, A437 (1965).

B. ACTINIDE CERAMIC COMPOUNDS

1. Antiferromagnetism of Uranium Monophosphide

(S. S. SIDHU, W. VOGELSANG,* AND K. D. ANDERSON)

Publication

S. S. Sindhu, W. Vogelsang,* and K. D. Anderson, *The Antiferromagnetism of Uranium Monophosphide*, J. Phys. Chem. Solids **27**, 1197 (1966).

The current investigation on the magnetic structure of UP has been published in considerable detail in the above reference. Uranium monophosphide has a NaCl-type structure, is paramagnetic at room temperature and antiferromagnetic at liquid nitrogen temperature. The chemical and magnetic unit cells are of the same size, however, the symmetry of the latter is tetragonal. The magnetic moments are aligned ferromagnetically

* Resident Research Associate from University of Wisconsin, Madison, Wisconsin.

in each layer but opposite in alternating layers perpendicular to the (001) plane. The magnetic moment at liquid-nitrogen temperature is 1.72 ± 0.02 Bohr magnetons. The magnetic form factors as determined from the observed reflections were compared with the values of the theoretical curve⁽¹⁸⁸⁾ on the assumption that the configuration of U^{+3} is $5f^3$ for which $S = 3/2$, $L = 6$ and $J = 9/2$. A $5f^3$ configuration appears to be consistent with the experiment. Another recent neutron study of this compound by Curry⁽¹⁸⁹⁾ is in basic agreement with a moment of 1.9 Bohr magnetons at 4°K, however, the strongest magnetic reflection shows a fairly abrupt change at about 30°K.

⁽¹⁸⁸⁾ Curry, N. A., Proc. Phys. Soc. London **86**, 1193 (1965).

⁽¹⁸⁹⁾ Curry, N. A., Proc. Phys. Soc. London **89**, 427 (1966).

2. Defect Equilibria in PuO_{2-x} (L. M. ATLAS AND G. J. SCHLEHMAN)

Publications

L. M. Atlas, G. J. Schlehman and D. W. Readey, *Defects in PuO_{2-x} : Density Measurements at High Temperature*, J. Am. Ceram. Soc. **49**, No. 11, 624-625 (1966).

L. M. Atlas and G. J. Schlehman, *Defect Equilibria of PuO_{2-x} , 1100 to 1600°C*, Thermodynamics, Vol. II, 407-421, Int. Atomic Energy Agency, Vienna (1966).

a. HIGH-TEMPERATURE DENSITY MEASUREMENTS

In order to identify the predominant defects in PuO_{2-x} , the densities of sintered polycrystalline samples were measured at 750°C in a gas pycnometer. Three series of experiments were carried out; each series started with measurements on $PuO_{2.0}$ produced by annealing specimens in moist helium at 1100 to 1200°C. The densities were then remeasured after reduction in a hydrogen/water-vapor mixture, and then once more after oxidation back to the original composition. In all cases the densities decreased after reduction and returned to nearly the original value

after reoxidation. These results, combined with lattice-constant data at 750°C⁽¹⁹⁰⁾ show that oxygen vacancies rather than interstitial cations are the predominant defects in PuO_{2-x} .

b. THERMODYNAMIC PROPERTIES OF PuO_{2-x}

A theoretical model of defects in MO_{2-x} compounds (described in section H on page 275) suggests that phase relations should be similar for the Ce-O and Pu-O systems. The Ce- HO system,⁽¹⁹¹⁾ which is well described by the theory, includes $CeO_{1.714}$ and $CeO_{1.67 \pm x}$ as separate phases above 600°C; however, their plutonium analogs have not been found.^(190,192) Since the solid phases in the Ce-O system are structurally similar, only small differences in free energy are involved in transformations; moreover, equilibrium is reached very

⁽¹⁹⁰⁾ Gardner, E. R., *The Plutonium-Oxygen Phase Diagram*, J. Inorg. Nucl. Chem. **27**, 541-551 (1965).

⁽¹⁹¹⁾ Bevan, D. J. M., and Kordis, J., *Mixed Oxides of the Type MO_2 (Fluorite)- M_2O_3 -I*, J. Inorg. Nucl. Chem. **26**, 1509-1523 (1964).

⁽¹⁹²⁾ Markin, T. L., and Rand, M. H., *Thermodynamic Data for Plutonium Oxides*, Thermodynamics, Vol. I, 145-156, Int. Atomic Energy Agency, Vienna (1966).

slowly. As a result, it is difficult to detect discontinuities in curves of oxygen potential vs. composition—especially if the measurements are carried out at discrete composition points as is the usual procedure. A more effective technique would be to perform an experiment in which continuous thermodynamic measurements are made during a slow composition traverse. An experiment of this kind is now in progress; it entails measuring the EMF drift of a solid-state, electrochemical cell,⁽¹⁹¹⁾

as it slowly oxidizes at constant temperature. Since

the electrode at the left contains two phases, the drift can be attributed to a change in composition of a single phase at the right. However, if the plutonium oxide transforms into a mixture at some point, an EMF arrest should occur until one of the phases disappears from either electrode. The desired slow oxidation rate is obtained by exposing the electrodes to a hydrogen-water vapor mixture (diluted by argon) corresponding to an equilibrium O/Pu ratio greater than 1.9. The composition of any new plutonium oxide phase can be estimated by quenching the cell at the time of an EMP arrest and analyzing the electrode.

3. Thermodynamic Properties of Plutonium Carbides (L. M. ATLAS AND G. J. SCHLEHMAN)

As a first step in the measurement of the thermodynamic properties of the plutonium carbides, cells described in ANL-7155 have been operated between 600 and 900°C with the fluorite electrolyte and electrodes indicated as follows:

Cells (1) and (2) were investigated to check the apparatus against results reported by Heuss and Egan⁽¹⁹³⁾ and by Aronson.⁽¹⁹⁴⁾ Agreement in both cases was within 0.005 volts, or 0.2 kcals in the free energy of the cell reaction.

Cell (3), although somewhat inconvenient to use because of the presence of molten plutonium at most temperatures of cell operation, was investigated in order to obtain data that would make possible the routine use of a plutonium carbide cell having solid electrodes. For example, a reference electrode made of a Th,ThF₄ mixture, which is solid, is more practical to use than a mixture of Pu and PuF₃. Use can then

⁽¹⁹³⁾ Heuss, R. J., and Egan, J. J., *Free Energies of Formation of Some Inorganic Fluorides by Solid State Electromotive Force Measurements*, Zeit. Physik. Chem. Neue Folge **49**, 38-43 (1966).

⁽¹⁹⁴⁾ Aronson, S., *Thermodynamic Properties of Thorium Carbides from Measurements on Solid EMF Cells*, Int. Symposium on Compounds of Interest in Nuclear Reactor Technology, IMD Special Report No. 13, 247-254, AIIME (1964).

45988

FIG. 209. Standard Free Energy of Formation of PuF₄.

be made of a plutonium carbide cell having the form

Subtracting the known EMF of cell (3) from that of cell (4) gives the EMF corresponding to the carbide reaction.

The Pu,PuF₃ electrode of cell (3) was prepared by heating together equal weights of PuF₄ and PuH₃. The net reaction occurring in cell (3) may be written as

and the corresponding standard free energy of this reaction is related to the cell EMF in volts by

$$\Delta F_{\text{Cell}}^{\circ} = -23,066 \text{ (EMF)}.$$

Combining reaction (5) with

gives

Accordingly, the standard free energy of formation per mole of PuF_3 is

$$\Delta F_{\text{PuF}_3}^{\circ} = 3\Delta F_{\text{Cell}}^{\circ} + \frac{3}{4}\Delta F_{\text{ThF}_4}^{\circ}, \quad (7)$$

where $\Delta F_{\text{ThF}_4}^{\circ}$ is the free energy of formation per mole of ThF_4 . Preliminary values of $\Delta F_{\text{PuF}_3}^{\circ}$ have been calculated on the basis that $\Delta F_{\text{ThF}_4}^{\circ} = -436.2$ kcal/mole at 600°C ⁽¹⁹⁴⁾ and the entropy $\Delta S_{\text{ThF}_4}^{\circ} \approx -71$ e.u. between 600° and 900°C .⁽¹⁹⁵⁾ The resulting curve of $\Delta F_{\text{PuF}_3}^{\circ}$ vs. T (Figure 209) is essentially linear between 600° and 900°C and the slope corresponds to $\Delta S_{\text{PuF}_3}^{\circ} \approx -62$ e.u. These free energies agree within about 2 kcal/mole with estimated values presented by Glassner.⁽¹⁹⁶⁾

⁽¹⁹⁵⁾ Darnell, A. J., *The Free Energy, Heat, and Entropy of Formation of Thorium Tetrafluoride*, NAA-SR-4924 (1960).

⁽¹⁹⁶⁾ Glassner, A., *The Thermochemical Properties of the Oxides, Fluorides, and Chlorides to 2500°K*, ANL-5750 (1957).

4. Neutron Diffraction Study of Neptunium Dioxide (M. H. MUELLER, L. HEATON, J. WILLIAMS, K. ANDERSON, D. ZAUBERIS, AND F. CAMPOS)

Recent measurements of Ross and Lam⁽¹⁹⁷⁾ had suggested that neptunium dioxide might become antiferromagnetic below approximately 30°K , and a transition of this type had been indicated some time previously by specific-heat measurements made by Osborne and Westrum.⁽¹⁹⁸⁾ Susceptibility measurements also suggested that neptunium carbide might undergo a ferro- and antiferromagnetic change.

In order to carry out a neutron-diffraction investigation of this material a thermal neutron scattering amplitude had to be determined. A 12 gm sample of the powdered oxide was welded in an aluminum thin-walled tube for safe handling. A neutron diffraction pattern was obtained with a $\lambda = 1.00\text{\AA}$ for each of several temperatures; namely, room temperature, 78 and 5.4°K , although only the room-temperature pattern was obtained to a relatively high 2θ . This latter pattern was indexed on the basis of a fluorite structure and absolute values of the structure factors, $|F_{hkl}|$, were obtained from a reference nickel sample. The reflections in which $h + k + l = 4n \pm 1$ or $4n$, which arise from metal atoms only or metal plus oxygen atoms, respectively, were relatively strong whereas the $4n + 2$ reflections, which are for metal-minus-oxygen

atoms, were practically nonexistent. The neptunium scattering amplitude must therefore be nearly equal to the oxygen scattering per unit cell. Results indicated that the b value for Np must be $1.0 \pm 0.1 \times 10^{-12}$ cm. Since some of the uncertainty in these results may have been due to (1) interference with the aluminum sample tube, (2) the sensitivity of the packing of the powder to shaking and tapping, and (3) the doubt about the oxygen-neptunium ratio, it was decided to repeat this determination.

TABLE 76. SUMMARY OF Np THERMAL NEUTRON SCATTERING AMPLITUDE RESULTS

hkl Type	Metal Oxygen Ratio	No. of Re- flections	Analysis By	Temp. Factor B		$b(\times 10^{-12} \text{ cm})$
				Np	O	
$4n \pm 1$	None re- quired	6	Graphical	-	-	1.051
$4n$	1:2.028	5	Graphical	-	-	1.053
$4n$ and $4n \pm 1$	1:2.028	11	Computer L.S.	0.04	0.10	1.055 ± 0.004
$4n$ and $4n \pm 1$	1:2.000	11	Computer L.S.	0.03	0.21	1.077 ± 0.019

⁽¹⁹⁷⁾ Ross, J. W., and Lam, D. J., *The Magnetic Susceptibility of Neptunium Oxide and Carbide Between 4.2°K and 350°K* , Presented at 12th Annual Magnetism Conference, Washington, D. C., November 1966.

⁽¹⁹⁸⁾ Osborne, D. W., and Westrum, E. F., *J. Chem. Phys.* **21**, 1884 (1953).

In the meantime the low-temperature patterns at 78 and 5.6°K were checked for the presence of antiferromagnetic lines. There appeared to be no real evidence for a (100), (110) or (210), one or more of which might

46001
FIG. 210. Neutron Diffraction Pattern of Neptunium Dioxide at 5.4°K in Which Only Nuclear Peaks are in Evidence.

45999
FIG. 211. Neutron Diffraction Pattern of UN at 5.4°K in Which a Magnetic (110) Peak and Nuclear Peaks Are Present.

be expected from an antiferromagnetic cell. Although there was no apparent difference between the two low-temperature patterns, both patterns upon further examination at low 2θ angles showed a rather high overall intensity that could be due to paramagnetic scattering. At this point in the investigation the chemical analysis was reported to be $\text{NpO}_{1.92}$ and in addition it was learned that a sample of this material that had been used for susceptibility measurements, had been fired in an oxidizing atmosphere to a reported $\text{NpO}_{1.94}$ composition.

Possible oxygen variations led us to be concerned as to the effect of oxygen on both the magnetic susceptibility measurements and/or the magnetic structure. This

was of special concern in view of the reported sensitivity of magnetic susceptibility of uranium dioxide to oxygen content as reported by Goldman and Arrott⁽¹⁹⁹⁾ and the more recent effect of oxygen on the magnetic structure of uranium dioxide as reported by Fraser, Shirane, and Cox.⁽²⁰⁰⁾

As a result of the above it was decided to fire the sample at 900°C in an oxidizing atmosphere and to use a vanadium sample tube for additional neutron diffraction patterns. Two patterns were made of the weighed

⁽¹⁹⁹⁾ Arrott, A., and Goldman, J. E., Phys. Rev. **108**, 948 (1957).

⁽²⁰⁰⁾ Fraser, B. D., Shirane, G., and Cox, D. E., Phys. Rev. **140**, A1448 (1965).

46000

FIG. 212. Neutron Diffraction Pattern of Uranium Dioxide at 5.4°K in Which Magnetic and Nuclear Peaks Are Present.

and measured sample at 78°K with and without a plutonium filter (to remove $\lambda/2$). Absolute values of the structure factors, $|F_{hkl}|$, for the individual reflections then underwent a graphical and computer least-squares treatment with the results shown in Table 76.

After we had completed the neutron diffraction pattern a chemical analysis for the oxygen was not available; therefore, b_{Np} was determined from the $2m + 1$ reflections, which have contributions from only metal atoms and are independent of the oxygen content. This value of b_{Np} was used to determine an oxygen-to-metal ratio from the $4n$ reflections. This procedure gave the composition $\text{NpO}_{2.032}$. When two chemical analyses became available they indicated the oxygen ratio as 1.953 and 2.103 for an average of 2.028. Later two additional chemical checks that were requested gave a 2.028 and 2.053 ratio. The average of four analyses is 2.034, which corresponds very well to the ratio, 2.032, determined by neutron diffraction. The range obtained by the chemical analysis may indicate that the sample may be heterogeneous in oxygen content, which could, of course, affect the magnetic susceptibility of the sample.

Two patterns were obtained at 5.4°K; with and without a plutonium filter. Since these patterns have just been obtained they have not been completely analyzed, however, a qualitative and limited quantitative evaluation of the patterns shows no additional evidence for an antiferromagnetic alignment. In fact, both temperature patterns appear identical. The pattern obtained at 5.4°K with a plutonium filter is shown in Figure 210.

It is highly important that magnetic-susceptibility and specific-heat measurements be made of the same samples as soon as possible. Approximately a 0.5 gm sample was retained of the original material used, as

well as the twice-oxidized sample. It is planned to pursue the magnetic problem of neptunium dioxide as well as neptunium carbide.

In the meantime we have been concerned with obtaining neutron diffraction patterns of antiferromagnetic compounds with a low magnetic moment and/or a material with a good likelihood of having a similar antiferromagnetic structure to NpO_2 , if one exists. A large sample of high purity UN was made for us by the Ceramics Group. Since its Curie point is 53°K a neutron diffraction pattern was obtained at 5.4 and 78°K.

The first magnetic peak (110) in UN is very evident in Figure 211. The magnetic structure of this compound was recently described by Curry,⁽²⁰¹⁾ who referred to "the intensity of the strongest magnetic reflection (110) being only $1/700$ of that of the strongest nuclear reflection (200)." Our measurements of these intensities indicate a 1:70.6 ratio and our calculation of his intensity ratio from his magnetic structure is 1:70. Therefore apparently Curry made an order-of-magnitude error in his statement. His magnetic-structure results will be unchanged, however, since he made his analysis from single-crystal data. The chemical analysis of this sample is not yet available.

We have also obtained a UO_2 sample that had been fired in hydrogen at 1700°C and vacuum desiccated for which a chemical analysis has been requested. Two neutron-diffraction patterns were obtained at 5.4 and 78°K since the Curie point for this material is 30.8°K. The lower-angle portion of the 5.4°K pattern is shown in Figure 212. A large number of magnetic lines are present at the low temperature; namely, (100) (110) (210) (211)

(201) Curry, N. A., Proc. Phys. Soc. **86**, 1193 (1965)

There is also good evidence of paramagnetic scattering in the liquid-nitrogen pattern.

A neutron pattern of $\text{UO}_{2.249}$ just obtained at 5.4°K

does not show any magnetic reflections and so demonstrates that the magnetic properties of UO_{2+x} are dependent upon the oxygen content.

5. Magnetic Susceptibilities of Actinide Carbides and Oxides (D. J. LAM AND J. W. ROSS)

The investigation of the magnetic properties of actinide compounds has been extended to include neptunium dioxide and neptunium carbide. The sample of neptunium dioxide was prepared by pressing NpO_2 powder, supplied by Oak Ridge National Laboratory, into a pellet and sintering it in an argon atmosphere for 105 minutes at 1400°C. The final composition of the pellet was $\text{NpO}_{1.94}$ with the following impurities in ppm: 200 of Fe, 200 of Pb, less than 1000 of Pu, 2000 of Th, 1000 of U, 100 of Ni, 100 of Si, 20 of Mn, 20 of Cu, 20 of Na, 10 of Cr and 10 of B. An X-ray powder pattern from a sample of this material was indexed as the CaF_2 -type structure with a lattice parameter of $5.434 \pm 0.001 \text{ \AA}$.

The temperature variation of the magnetic susceptibility (χ) of neptunium dioxide is shown in Figure 213. The peak in the susceptibility curve at 25°K is

43793

FIG. 213. The Molar Susceptibility of Neptunium Dioxide.

consistent with the maximum in the specific heat curve obtained by Westrum, et al.⁽²⁰²⁾ Our result sup-

⁽²⁰²⁾ Westrum, E. F. Jr., Hatcher, J. B., and Osborne, D. W., "The Entropy and Low Temperature Heat Capacity of Neptunium Dioxide," J. Chem. Phys. **21**, 419-423 (1953).

43792

FIG. 214. The Magnetization of Neptunium Carbide Above 200°K.

43791

FIG. 215. The Magnetization of Ferromagnetic Neptunium Carbide.

ports their suggestion that neptunium dioxide is antiferromagnetic with a Néel temperature of 25°K. Above 60°K the inverse susceptibility is linear with temperature and the gradient of this line gives an effective paramagnetic moment of $2.95 \mu_B$.

The NpC was prepared by arc melting Np metal with high-purity graphite in an argon-helium atmosphere. The resulting button was heat treated at 1430°C

for $2\frac{1}{2}$ hours. The X-ray powder pattern indicated that the sample was single phase with a lattice parameter of $4.994\text{\AA}$, but microscopic examination revealed a small amount of the residual cored structure.

The magnetization per gram in fields of 7.25 kOe and 10.28 kOe from 200 to 330°K is shown in Figure 214. Below 200°K , NpC is ferromagnetic. The magnetization versus temperature curve is shown in Figure 215. Below 110°K the magnetization is independent of field strength between 1 and 11 kOe. Thus a reliable value of $1.4 \mu_B$ can be assigned to each NpC unit in

the ferromagnetic state of NpC. The peak in susceptibility at 310°K indicates a transition from a magnetically ordered arrangement to a paramagnetic one. In the limited range from 310°K to 350°K , where $1/\chi$ is linear with temperature, an effective paramagnetic moment of approximately $3.0 \mu_B$ is deduced. Recent measurements, up to 1000°K , yield a more accurate value of $3.37 \mu_B$ per NpC unit.

A parallel study of the magnetic properties of these compounds by neutron diffraction techniques is in progress (Mueller and Heaton, page 222).

C. DEFORMATION AND PLASTICITY

1. Fatigue Properties of Single Crystals and Polycrystals (PENTTI O. KETTUNEN)

Connecting cross-slip is an important mechanism in various theories of fatigue.^(203,204) Experimentally it has been observed in "fatigue striations" on a crystal surface (see e.g. Ref. [205]). On the other hand, cross-slip has been proposed to be responsible for stage III in unidirectional deformation,⁽²⁰⁶⁾ and again a correlation with surface slip bands has been found.⁽²⁰⁷⁾ The suggestion has therefore been made that there is a correlation between fatigue deformation and the unidirectional deformation in stage III.⁽²⁰³⁾ Such a correlation can best be tested if the fatigue tests are done at constant stress amplitude. A descriptive result of fatigue tests at constant stress amplitude is a curve relating the stress amplitude to the number of cycles to failure, the "S-N curve." In tests of this kind the endurance limit has in fact been found to be of the same order of magnitude as τ_{III} , the stress at the onset of stage III.^(208,209)

If such a correlation does indeed exist, it might be expected to occur not only in metals of fcc lattice structure, but also in those bcc metals in which a stage III of work-hardening has been observed.^(210,211) Furthermore, it should be observed not only in single crystals but also in polycrystals, since they, too, exhibit stage III work-hardening.⁽²¹²⁾

For a comparison of polycrystals with single crystals, the S-N curves have to be converted to shear stress on the active slip systems. The effective orientation factor, M , for polycrystals should be the one based on polyslip, and is 3.06 for fcc metals.⁽²¹³⁾ In

bcc metals, the factor is the same if slip occurs on $\{110\}$ planes; for the case in which the deformation is more closely described by pencil glide, Kocks* has given a lower limit of 2.65 for the effective orientation factor, and Hutchinson⁽²¹⁴⁾ has derived an approximate value of 2.74. For the case in which crystallographic slip takes place partly on $\{110\}$ planes and partly on others, the effective orientation factor should be between these extreme values of 2.65 and 3.06. Thus, 2.85 is always correct within $\pm 7\%$.

The comparison between polycrystal and single crystal behavior might be complicated by an orientation dependence of the single-crystal endurance limit, which should be expected from the rather strong orientation dependence of τ_{III} . The most relevant orientations for this comparison are the symmetric ones which also exhibit polyslips.⁽²¹⁵⁾ However, there does not seem to be such an experimental evidence for the orientation dependence of fatigue properties, because most results reported show only slight or negligible influence of orientation on the S-N curve (see e.g. Refs. [216 and 209]).

The behavior of polycrystals can be influenced also by the grain size. In the case of iron, for example, the endurance limit was found to decrease with increasing grain size, up to a limiting grain size above which the endurance limit remained essentially constant.⁽²¹⁷⁾ If this observation is of general validity, polycrystals of sufficiently large grain sizes should be used for comparison with single crystals; otherwise, the grain-size dependence has to be known quantitatively.

To test some of the ideas outlined above, we have re-evaluated our own data as well as those available in the literature in which both the polycrystals and single crystals were tested at constant stress amplitude. Apparently, such data exist only for copper and iron.

Figure 216 shows the S-N curve of iron single crystals.

* Unpublished work reported at Metal Physics Discussion Meeting at Muellendorf, Germany.

⁽²¹⁴⁾ Hutchinson, J. W., *J. Mech. Phys. Solids*, **9**, 16 (1964).

⁽²¹⁵⁾ Kocks, U. F., *Acta Met.*, **6**, 85 (1958).

⁽²¹⁶⁾ Hempel, M. R., *Symp. Basic Mech. of Fatigue*, ASTM Spec. Publ. No. 237, ASTM Philadelphia, Pa., p. 52 (1959). (See also *Fracture*, ed. Averbach et al., The Tech. Press of MIT and John Wiley and Sons, Inc., New York, 1959, p. 376).

⁽²¹⁷⁾ Kettunen, P. O., *Lic. Tech. Thesis*, Institute of Technology, Helsinki, Finland (1963).

⁽²⁰³⁾ Feltham, P., *Proc. Roy. Soc.*, **A242**, 158 (1957); and *Phil. Mag.*, **3**, 806 (1958).

⁽²⁰⁴⁾ Mott, N. F., *Acta Met.*, **6**, 195 (1958).

⁽²⁰⁵⁾ Grosskreutz, J. C., *Proc. 10th Sagamore Army Research Conf.*, ed. Burke et al., Syracuse University Press, Syracuse, New York, p. 27 (1964).

⁽²⁰⁶⁾ Diehl, J., Mader, S., and Seeger, A., *Z. Metallk.*, **46**, 650 (1955).

⁽²⁰⁷⁾ Mader, S., *Zeitschr. f. Physik*, Bd 149, 73 (1957).

⁽²⁰⁸⁾ Ham, R. K., and Broom, T., *Phil. Mag.*, **7**, 95 (1962).

⁽²⁰⁹⁾ Kettunen, P. O., *D. Tech. Thesis*, Institute of Technology, Helsinki, Finland (*Acta Polytechnica Scand.*, Ch 38) (1965).

⁽²¹⁰⁾ Mitchell, T. E., Foxall, R. A., and Hirsch, P., *Phil. Mag.*, **8**, 1895 (1963).

⁽²¹¹⁾ Keh, A. S., *Phil. Mag.*, **12**, 9 (1965).

⁽²¹²⁾ Kocks, U. F., Chen, H. S., Rigney, D. A., and Schaefer, R. J., to be published in *AIME Symposium on Work Hardening*, ed. Hirt and Weertman, Gordon and Breach (1967).

⁽²¹³⁾ Taylor, G. I., *J. Inst. Metals*, **62**, 307 (1938).

45961

FIG. 216. S-N Curves of Single Crystalline and Polycrystalline α -iron Containing about 0.006% Carbon (Hempel, 1959).

45962

FIG. 217. The Data of Figure 216 Replotted. The circles correspond to crystals oriented initially inside the standard stereographic triangle, the crosses correspond to crystals oriented initially on an edge of the stereographic triangle, and the triangles correspond to polycrystals. Shear stress amplitudes in single crystals are calculated in the slip system (101)[11 $\bar{1}$], and those in polycrystals are calculated for $\bar{M} = 2.85$.

45963

FIG. 218. Comparison of Fatigue Strength Properties of Iron and Copper. The continuous solid line is the S-N curve of Figure 217, the circles correspond to results with copper single crystals (Kettunen, 1965, 1966), and the triangles correspond to results with copper polycrystals (Thompson et al., 1956). Shear stress amplitudes in copper single crystals are calculated in the slip system (11 $\bar{1}$)[101], and those in copper polycrystals are calculated using $\bar{M} = 3.06$.

tals and polycrystals reported by Hempel.⁽²¹⁶⁾ Figure 217 shows the same data resolved on the slip system (101)[11 $\bar{1}$]. When the same results are plotted on the basis of pencil slide, the figure looks similar.⁽²¹⁸⁾ The points for polycrystals and single crystals overlap over most of the range; but any significance of the deviation at short fatigue lives is unknown. Also, the scatter between single crystals of various orientations appears to be small. In Figure 217, all crystals that were initially oriented for multiple slip are plotted as x whereas those originally oriented for single slip are plotted as o . If there is any difference at all, it is such as to make the fatigue life of crystals of multiple slip slightly shorter than that of crystals of single slip; this result is similar to that reported by Kettunen⁽²¹⁹⁾ for copper crystals.

In his report, Hempel does not mention the grain size of the iron polycrystals. A comparison with Kettunen's results on high-purity iron⁽²¹⁷⁾ suggests that the grain size of Hempel's specimens must have been near 0.2 mm. This value is slightly above the limiting grain-size value and thus a comparison with single crystals is meaningful.

The solid line drawn in Figure 217 is transferred to Figure 218 for a comparison of the results with copper. The results here show stress amplitudes normalized by the shear moduli: for iron, $G = 75$ kg/mm²; for copper, $G = 4201$ kg/mm².

⁽²¹⁸⁾ Kettunen, P. O., to be published (1967).

⁽²¹⁹⁾ Kettunen, P. O., Phil. Mag., **14**, 421 (1966).

The present results on copper single crystals^(209,219) seem to follow a pattern similar to that in iron, but at slightly lower normalized stress amplitudes. Corresponding values for copper polycrystals were difficult to find. McCommon and Rosenberg⁽²²⁰⁾ have reported S-N curves, but did not specify the grain size; furthermore they used a rather low annealing temperature. While Thompson et al.⁽²²¹⁾ also used a low annealing temperature, they were careful to cool slowly after annealing, and reported a grain size of about 0.1 mm. Their results are shown in Figure 218 and are significantly above those for single crystals. This is at least partly a result of the grain size; also, the much higher frequency used (1000 cps vs. 30 cps) may have had an influence in the same direction. In any case, for results obtained by different investigators, the agreement between polycrystals and single crystals is close enough. This suggests that the applied shear stress amplitude is an important parameter in fatigue and may be the determining one.

⁽²²⁰⁾ McCommon, R. D., and Rosenberg, H. M., Proc. Roy. Soc. A, **242**, 203 (1957).

⁽²²¹⁾ Thompson, N., Wadsworth, N., and Louat, N., Phil. Mag., **1**, 113 (1956).

Figure 218 shows that even the two very different metals, iron and copper, give very similar results. This would be expected if there is a correlation between fatigue and unidirectional deformation in stage III, because the ratios τ_{III}/G happen to be very similar for copper and iron at room temperature. This coincidence of curves in Figure 218 is not, however, any sufficient proof for the existence of any correlation with stage III. A much more discriminating test would be a comparison of these results with those on aluminum on which τ_{III}/G is about half as large. Although the results reported by Roberts and Honeycombe⁽²²²⁾ for fatigue lives of aluminum single crystals show a large scatter, they do suggest that the endurance limit must be below 0.7 kg/mm². The corresponding τ_w/G ratio of 0.28×10^{-3} is approximately half of that for iron and copper. On this basis, a correlation between fatigue and unidirectional deformation in stage III might be possible.

I want to thank Dr. A. S. Keh of United States Steel Corp. for providing the G-values of iron.

⁽²²²⁾ Roberts, E., and Honeycombe, R. W. K., J. Inst. Metals, **91**, 134 (1962).

2. Statistical Theory of Flow Stress and Work-Hardening (U. F. KOCKS)

A common feature of all theories of flow stress, be it in work hardened, solution hardened, precipitation hardened, or dispersion hardened materials is that a dislocation element moving through a crystal encounters a varying resistance; in other words, there are "soft spots" and "hard spots". The spacing between the hard spots enters inversely into the flow stress in all such theories. While it is an uncontested fact that the spacing between neighboring obstacles is not uniform throughout the crystal, it has been considered sufficient to use some average spacing in the flow stress relation just as if the obstacles were arranged in a *regular* pattern.

We have taken the opposite approach and have analyzed the case of a *random* distribution of obstacles. For the purposes of a specific calculation, the obstacles were assumed to be points distributed at random on a slip plane. Under the action of an externally applied stress, any dislocations that might be lying in this slip plane will bow out, by varying amounts, between "neighboring" obstacle points, and the series of obstacle points it touches will not in general lie along a straight line. At each of these obstacle points, the two branches of the dislocation will

enclose an angle smaller than 180° and will thus exert a force on the obstacle. If the angle is smaller than a critical "breaking angle", the obstacle gives way under the force. This "breakthrough" is one of the two major mechanisms of local yield, the other one being "bowing-out" of the dislocation into a half-loop between neighboring obstacle points.

A small dislocation loop that spreads under a given applied stress may eventually find itself in front of a series of obstacles that it can neither break through nor bow out between. The area the loop has covered before being thus blocked, will be larger the greater the stress. On the other hand, concurrent lengthening of the dislocation increases the number of potentially weak spots, and each of them acts like a new source. The result is a catastrophic increase in the area swept out by the dislocation at some critical stress. Since the plastic strain is proportional to the area swept out by the dislocation, this process may be what defines the macroscopic flow stress. Figure 219 shows the average area covered as a function of an applied stress which is less than the flow stress. This figure may be read as a stress-strain diagram at constant structure (no work-hardening). The curve marked $f = 1$ repre-

106-8940 Rev. 2

FIG. 219. Average Area Swept Out by Dislocations, in Units of the Average Area per Obstacle, at a Given Fraction of the Flow Stress: $f = 1.0$, Strong Obstacles; $f = 0.5$, Breaking Angle 120° .

106-8937 Rev. 1

FIG. 220. Flow Stress in Units of $2E/bl$ (E is the Line Energy of Edge Dislocation, b is the Burgers Vector, l is the Square Root of Average Area per Obstacle), as a Function of Obstacle Strength.

sents strong obstacles, so that only bow-out processes contribute to yield; $f = 0.5$ means weaker obstacles.

Even when the applied stress is equal to the flow stress, there will be some hard spots, i.e. a series of closely spaced obstacles, which have to be surrounded by the dislocation. A concave loop will be left around every one of these hard spots by every dislocation that has spread through the glide plane. The ensuing increase in the dislocation density with strain constitutes a basic mechanism for work-hardening, which leads to a quantitative explanation of the hardening rate in "stage II".⁽²²³⁾

At a given spacing of the obstacles, the flow stress depends on their strength. If the array of obstacles were regular, this dependence would be of the cosine of half the breaking angle. For our random distribution, the theoretical result is shown in Figure 220. This result was obtained⁽²²⁴⁾ by an analytical statistical method; an electronic computer was used only for the evaluation of integrals. For comparison, Figure 220 shows points derived by Foreman and Makin⁽²²⁵⁾ from a computer model study. The significant feature of these results is that the flow stress predicted is always lower than that following from a regular array, by roughly 20% in the case of strong obstacles.⁽²²⁶⁾ This is in contrast to proposals advanced in connection with dispersion strengthening⁽²²⁷⁾ where the flow stress is related to the spacing of *nearest-neighbor* obstacles, and amounts to twice the flow stress in a regular array.

Breakthrough processes can be thermally activated, so that the flow stress may be dependent on temperature and strain-rate provided a first-order change in the breaking angle leads to a first-order change in the necessary dislocation curvature. The

ratio of the latter to the former is sometimes referred to as the "activation length", and this parameter has been evaluated from the present theory.⁽²²⁴⁾ The results indicate that the effect of such thermal activation processes on the flow stress should be very low for very weak obstacles as well as very strong ones; it is of the order commonly assumed only for obstacles of intermediate strength. A special feature of these results is that for obstacles that are *almost* strong enough to resist breakthrough, thermal activation should be most effective.

Finally, the model lends itself to a theoretical treatment of processes that do not occur at constant strain rate, such as creep, stress relaxation, and stress cycling. In these cases, either the applied stress decreases, or the flow stress increases while the applied stress stays constant. The ratio of applied stress to flow stress thus decreases continuously and, as a consequence, the free slip area becomes smaller with time. Dislocation pile-ups should develop which eventually prevent any further strain from taking place under the applied stress.

In the particular case of fatigue at constant stress amplitude Kettunen and Kocks⁽²²⁸⁾ have speculated that the amount of hardening during the first few hundred cycles may determine the size of the free slip area during "saturation"; if this area is of the order of magnitude of the average area per obstacle, all deformation should be reversible and no fracture should ever occur. On the other hand, if individual dislocation loops can expand and contract, during the saturation period, over an area containing many obstacles, it is possible in principle for irreversible structural changes to take place that may eventually lead to fracture. Thus, a sufficiently low rate of work-hardening would be a necessary (but not a sufficient) condition for fatigue fracture to occur. It is possible that this condition alone leads to the observed correlation of the endurance limit with τ_{III} in unidirectional deformation.^(229,230)

⁽²²³⁾ U. F. Kocks, *Phil. Mag.* **13**, 541 (1966).

⁽²²⁴⁾ U. F. Kocks, *Can. J. Phys.* to be published (presented at International Conference on Deformation of Crystalline Solids in Ottawa, August 1966).

⁽²²⁵⁾ A. J. E. Foreman and M. J. Makin, *Phil. Mag.* **14**, 911 (1966).

⁽²²⁶⁾ U. F. Kocks, *Acta Met.* **14**, 1629 (1966).

⁽²²⁷⁾ K. H. Westmacott, C. W. Fountain and R. J. Stirton, *Acta Met.* **14**, 1628 (1966).

⁽²²⁸⁾ P. O. Kettunen and U. F. Kocks, to be published.

⁽²²⁹⁾ R. K. Ham and T. Broom, *Phil. Mag.* **7**, 95 (1962).

⁽²³⁰⁾ P. O. Kettunen, *Acta Polytech. Scand.*, Ch. 38 (1965).

3. The Importance of Twinning for the Ductility of CPH Polycrystals (U. F. KOCKS)

While single crystals of most materials with CPH lattice structure show essentially unlimited ductility, polycrystalline specimens of the same materials exhibit the entire range of ductilities. A difference between the ductility of single crystals and polycrystals

may be associated with the special stress concentrations to be expected, for example, at the intersections of slip bands or twin lamellae with grain boundaries. Whether such stress concentrations prove catastrophic, depends on the cleavage strength of the material, the

size of the stress concentrations, and the speed with which they are formed. Thus, the ductility may vary in degree from material to material.

Another possible reason for differences in ductility between single crystals and polycrystals is that a sufficient number of independent deformation modes must be available to insure compatibility between the macroscopic strains in neighboring grains.^(231, 232) This criterion is often taken to be a necessary condition for any polycrystal ductility whatsoever, not as one that determines different degrees of ductility; thus, a material with an insufficient number of independent deformation modes would have to be brittle as a polycrystal. The "sufficient number" is five if every grain is to accommodate arbitrary shape changes ("von Mises criterion").⁽²³³⁻²³⁵⁾

We should like to argue that fewer than five independent modes may be sufficient to satisfy compatibility conditions; and that the internal stresses set up when the plastic strains are not compatible, reach the theoretical fracture stress only after occurrence of a significant amount of macroscopic strain, which may vary in magnitude from case to case and thus allow an influence on the *degree* of ductility.

Experimental evidence for these statements is taken from the following review of the number of independent deformation modes observed in the various CPH materials. As an "observed mode" we count in this connection only such modes for which traces were observed away from special stress concentrations, such as at grain corners, etc.: compatibility has to be satisfied everywhere.

Table 77 shows in which of the three major slip system types "extensive" slip has, in our judgment, been observed, and the order of abundance (or the order of increasing temperatures at which they began to be extensively observed). Slip on the prism plane in the c -direction, even if it were observed, would provide the identical modes as does basal slip. Slip on a pyramidal plane was not included unless the Burgers vector had been observed to be in the $(c + a)$ direction, and then the plane is usually $\{11\bar{2}2\}$. Slip on a $\{10\bar{1}1\}$ plane is occasionally observed, but then it is generally assumed to be in the a -direction; this corresponds to a mode that can also be obtained by a combination of basal and prism slips.

The two most common slip system types, basal and prism slip, have only four independent modes between them.⁽²³⁴⁾ Thus, $(c + a)$ slip is necessary, and it is by

itself sufficient,⁽²³⁵⁾ to fulfill a von Mises criterion based on slip alone. Pyramidal $(c + a)$ slip has been observed in cadmium,^(236, 237) zinc⁽²³⁸⁾ and beryllium.⁽²³⁹⁾ (The abundance decreases considerably from Cd to Zn and from Zn to Be, and so do the ductilities: an interesting case of a possible influence of the number of slip modes on the *degree* of ductility.) Yet rhenium,^(240, 241) titanium,⁽²⁴²⁻²⁴⁴⁾ and zirconium^(245, 246) exhibit essentially unlimited ductility although $(c + a)$ slip has never been identified in any of them, and although in zirconium even basal slip seems to be of little consequence.

The behavior of these materials, among others,* has led other authors to include twinning systems as possible deformation modes for the purposes of satisfying compatibility conditions.⁽²⁴⁹⁾ We see no other recourse, because two independent slip modes unquestionably offer too few possibilities of accommodation. Experimentally, this is confirmed by the observed brittleness of a Cd-Mg alloy⁽²³⁶⁾ in which twinning had been eliminated by making $c/a = \sqrt{3}$.

There are three common objections to counting twinning modes as contributing to an increase in ductility. The first is related to the stress concentrations already mentioned; it eliminates the possibility of applying this treatment to "notch sensitive" materials. The second concerns the limited amount of deformation achieved even when the entire volume has been twinned. The table shows the magnitude of the twinning shear for those materials in which the respective system has been extensively observed, and also gives the resolved components of this strain that lead to an extension in the c -direction and to a shear in the basal plane. It

* Materials of orthorhombic or lower symmetry slip in only one direction, if at all, yet generally twin profusely. Some, like α -U, are reasonably ductile even in polycrystalline form.⁽²⁴⁸⁾

(236) N. S. Stoloff and M. Gensamer, *Trans. Met. Soc. AIME* **227**, 70 (1963).

(237) W. J. McG. Tegart, *Phil. Mag.* **9**, 339 (1964).

(238) R. L. Bell and R. W. Cahn, *Proc. Roy. Soc. A* **239**, 494 (1957).

(239) D. Beasley and A. Moore, in *Beryllium Technology*, Gordon and Breach (AIME), (1966).

(240) A. T. Churchman, *Trans. Met. Soc. AIME* **218**, 262 (1960).

(241) R. A. Jeffery and E. Smith, *Phil. Mag.* **13**, 1163 (1966).

(242) F. D. Rosi, C. A. Dube, and B. H. Alexander, *Trans. Met. Soc. AIME* **197**, 257 (1953).

(243) E. A. Anderson, D. C. Jillson, and S. R. Dunbar, *Trans. Met. Soc. AIME* **197**, 1191 (1953).

(244) A. T. Churchman, *Proc. Roy. Soc. A* **226**, 216 (1954).

(245) J. L. Martin and R. E. Reed-Hill, *Trans. Met. Soc. AIME* **230**, 780 (1964).

(246) D. G. Westlake, unpublished results.

(247) D. G. Westlake, *Acta Met.* **9**, 327 (1961).

(248) A. N. Holden, *Physical Metallurgy of Uranium*, Addison-Wesley (1958).

(249) R. E. Reed-Hill, in *Deformation Twinning*, Gordon and Breach (AIME), (1964).

(231) G. I. Taylor, *J. Inst. Met.* **62**, 307 (1938).

(232) U. F. Kocks, *Acta Met.*, **6**, 85 (1958).

(233) R. von Mises, *Z. Angew. Math. Mech.* **8**, 161 (1928).

(234) G. W. Groves and A. Kelly, *Phil. Mag.* **8**, 877 (1963).

(235) U. F. Kocks, *Phil. Mag.* **10**, 187 (1964).

TABLE 77. TWINNING SHEAR S , RESOLVED c -EXTENSION ϵ , AND RESOLVED BASAL SHEAR γ , FOR OBSERVED TWINNING SYSTEMS; AND OBSERVED SLIP SYSTEMS IN ORDER OF ABUNDANCE

Element	c/a	Twinning System Types									Slip System Types		
		{10 $\bar{1}$ 2} <1011>			{11 $\bar{2}$ 1} <1126>			{11 $\bar{2}$ 2} <1123>			{0001}	{11 $\bar{0}$ 0}	{11 $\bar{2}$ 2}
		S	ϵ	γ	S	ϵ	γ	S	ϵ	γ	<11 $\bar{2}$ 0>	<11 $\bar{2}$ 0>	<11 $\bar{2}$ 3>
Cd	1.886	-0.171	-0.085	± 0.015		—			—		1	3	2
Zn	1.856	-0.138	-0.069	± 0.010		—			—		1	3	2
Mg	1.624	+0.129	+0.064	± 0.008		—			—		1	2	—
Re	1.614	+0.141	+0.070	± 0.010	+0.620	+0.175	± 0.511	-0.250	-0.112	± 0.111	1	2	—
Ti	1.602 ^(a)	+0.156	+0.078	± 0.012	+0.624	+0.178	± 0.513	-0.236	-0.106	± 0.104	2	1	—
Zr	1.592	+0.169	+0.084	± 0.014	+0.628	+0.180	± 0.515	-0.224	-0.101	± 0.097	—	1	—
Y, Hf, Gd	1.587 ^(a)	+0.175	+0.087	± 0.015	+0.630	+0.181	± 0.516		—		2	1	—
Dy, Ho, Er	1.58	+0.184	+0.092	± 0.017	+0.633	+0.182	± 0.518		—		2	1	—
Be	1.568	+0.199	+0.099	± 0.020		—			—		1	2	3

^(a) c/a values for Ti are variously given as 1.587 and 1.602, those for Hf as 1.587 and 1.581. The two latter figures, as well as all other c/a values, are from *Crystal Data*, 2nd ed., Amer. Cryst. Assoc. (1963).

Formulae: The twinning shear S for the three types is $(a/c) (3 - (c/a)^2)/\sqrt{3}$; a/c ; and $(2/3) (a/c) (2 - (c/a)^2)$, respectively.⁽²⁴⁷⁾ If the twinning vector is $[hkl]$, and $L^2 = (3/2) (a/c)^2 (h^2 + i^2 + k^2)$, then ϵ , the c -extension per unit twinning shear, is $lL/(l^2 + L^2)$, and γ , the maximum shear in the basal plane per unit twinning shear, is $(l^2 - L^2)/(l^2 + L^2)$.

is seen that in no case is the strain larger than 65% and in most it is of the order of 10%. The strain is not limited, however, if twinned volumes may re-twin or re-slip, as has been frequently observed; this must be the reason for the obvious unimportance of this objection in the cases of zirconium, titanium, and rhenium.

A final argument against the importance of twinning in polycrystal ductility is that it occurs in one direction only so that, for example, in a particular material it can accommodate either c -extension or c -contraction but not both. We see from the table that the cases just discussed, viz. rhenium, titanium, and zirconium happen to have twinning systems that lead to a c -extension and others that lead to a c -contraction. The especially large ductility shown by these materials must be due to this profusion of twinning systems. It is also worth noting that the absence of basal slip in zirconium is of no particular consequence since the major twinning mode, $\{11\bar{2}1\} \langle \bar{1}126 \rangle$, gives a resolved shear of about 50% on the basal plane.

If both "positive" and "negative" twinning occur, the independent deformation modes provided by twinning are exactly the same as those from $(c + a)$ pyramidal slip, viz. all five. The large ductility of rhenium, titanium, and zirconium polycrystals is thus easily explained. Yttrium, hafnium, and the rare earths gadolinium, dysprosium, holmium, and erbium have also been shown to have tensile elongations approaching 10%, and they can be worked extensively.⁽²⁵⁰⁾ Yet in extensive surface observations,⁽²⁴⁶⁾ we have never

seen the twinning mode that gives c -contraction. Furthermore, basal slip has only been observed rarely and at places where stress concentrations may be expected. Of the five independent deformation modes available, only two are thus "full" modes, the other three are unidirectional. The conclusion is unescapable that compatibility can be maintained, for some considerable amount of strain at least, by fewer than five full modes and that, in particular, the unidirectionality of twinning is of surprisingly little importance.

The same conclusion can be arrived at from the results on magnesium at high temperatures and Mg-Li alloys at lower temperatures.⁽²⁵¹⁾ Here, both basal and prism slip are observed; a special twinning mode, on a $\{10\bar{1}1\}$ plane, has been seen only at places of special stress concentration.⁽²⁵²⁾ Thus, there are four full modes and one unidirectional one. The polycrystal ductility is considerable.

In the light of these observations, the lack of ductility in magnesium,⁽²⁵¹⁾ zinc,⁽²⁵³⁾ and beryllium⁽²⁵⁴⁾ polycrystals at low temperatures, where basal slip plus unidirectional twinning is observed, cannot be due to a lack in the number of independent modes. Presumably it must be ascribed to a sensitivity of these materials to stress concentrations.

From a phenomenological point of view, we conclude that, while unlimited ductility is only possible with five

⁽²⁵¹⁾ F. E. Hauser, P. R. Landon, and J. E. Dorn, *Trans. ASM* **50**, 856 (1958).

⁽²⁵²⁾ B. C. Wonsiewicz and W. A. Backofen, *Trans. Met. Soc. AIME*, in press (1967).

⁽²⁵³⁾ G. W. Greenwood and A. G. Quarrell, *J. Inst. Met.* **82**, 551 (1953).

⁽²⁵⁴⁾ A. P. Green and J. Sawkill, *J. Nucl. Mat.* **3**, 101 (1961).

⁽²⁵⁰⁾ B. Love and C. Kirkpatrick, in *Rare Earth Research*, Macmillan (1961).

full, independent deformation modes, the absence of some modes, especially unidirectional ones, only decreases the *degree* of ductility; about 10 % tensile elongation can be obtained by one type of slip plus one type of twinning such as are observed in any one of the CPH elements at all temperatures. If brittleness is observed, it must be due to other causes. This view is in accord with that of Conrad⁽²⁵⁵⁾ but different from that of various other authors.⁽²⁵⁶⁾

It remains to be discussed how the compatibility conditions on macroscopic plastic strains can be fulfilled in a polycrystal with less than five independent deformation modes. If a particular grain had five independent deformation modes available, it could accommodate any strain conditions imposed by the surroundings. If there is a particular strain component it cannot provide,

⁽²⁵⁵⁾ H. Conrad and I. Perlmutter, in *Conférence Internationale sur la Métallurgie du Béryllium*, p. 326, Presses Universitaires de France (1966).

⁽²⁵⁶⁾ D. McLean, *ibid.*, p. 3.

this grain will in turn impose conditions on its surroundings. In the absence of a correlation between the orientations of neighboring grains (unfortunately, a rather academic case), the surrounding grains should be able to accommodate this condition fairly well when there is only one mode missing, less well when there are two missing, etc. Only that component of the unsatisfied strain which is parallel to the macroscopically imposed strain, should be correlated between randomly oriented grains, and this component should be roughly one order of magnitude smaller than the macroscopic strain. It is not surprising that, under such conditions, a large degree of ductility can be obtained, and that this ductility may vary by *degree* from material to material.

If only a *unidirectional* mode is missing, half the surrounding grains will, on the average, be able to fulfill any condition whatsoever. It is thus not likely that a series of contiguous grains can be found all of which are unable to fulfill a particular prescribed strain component; only then should the sample be brittle.

4. Habit Plane of the Hydride in Zirconium (D. G. WESTLAKE)

Publication

D. G. Westlake, *On Stress Orientation of Zirconium Hydride in a Single Crystal of Zirconium*, Trans. Met. Soc. AIME **236**, 1229 (1966).

There is a growing consensus that a tensile stress applied on a rod of polycrystalline zirconium-hydrogen alloy during slow cooling will cause hydride platelets to be precipitated perpendicular to the tensile axis. The publication above describes an experiment per-

formed on a single crystal to test the hypothesis⁽²⁵⁷⁾ that precipitation of the low-density hydride will occur in the plane that will result in the maximum relief of stress. We have shown that the maximum stress one can apply without introducing gross plastic strain as another variable is insufficient to cause stress orientation of zirconium hydride in a single crystal of zirconium.

⁽²⁵⁷⁾ Louthan, M. R., Jr., and Angerman, C. L., Trans. Met. Soc. AIME **236**, 221 (1966).

5. Hydrogen Embrittlement of Vanadium and Niobium (D. G. WESTLAKE)

Publication

D. G. Westlake and W. R. Gray, *A Pitfall in the Preparation of Metal-Hydrogen Alloys for Transmission Electron Microscopy*, Applied Physics Letters **9**, 3-4 (1966).

The 1965 Annual Report (ANL-7155) describes attempts to ascertain the disposition of hydrogen in niobium and vanadium at low temperatures by transmission electron microscopy. The investigation had been initiated to gain an understanding of the

mechanism of hydrogen embrittlement of bcc hydride formers.

The observed manifestations of ordering of hydrogen in preferred interstitial sites of vanadium and niobium had not been anticipated for the alloys of low hydrogen concentration with which we were dealing. Therefore, we deemed it necessary to investigate the possibility that our specimens were not representative of the bulk material, i.e., that our electrothinning techniques were, in some way, increasing the hydrogen concentration. The publication above de-

scribes three electrothinning baths for vanadium, one for niobium, and one chemical thinning bath for tantalum, all of which produced microscope samples with hydrogen concentrations higher than the starting material. Only in zirconium, thinned chemically, did the hydrogen concentration remain constant.

Subsequently, we have developed several other thinning techniques and have studied the effects of these and of grinding on the hydrogen concentration in vanadium. The results of particular experiments shown in Table 78 are typical. Each of the chemical and electrothinning techniques produced foils that were thin enough for transmission electron microscopy but they were far from representative of the bulk with respect to hydrogen concentration. The grinding experiments demonstrate that a freshly exposed vanadium surface is highly reactive in water or methanol. Furthermore, the hydrogen introduced during grinding must be extremely mobile to escape removal by subsequent grinding.

On the basis of these results, the prospect of thinning vanadium without changing the hydrogen concentration seemed very remote. Therefore, the following experiment was designed as a different approach to the study of hydrogen embrittlement by transmission electron microscopy.

If hydrogen were precipitated as vanadium hydride at the embrittlement temperature, then during deformation dislocations might be pinned, pile-ups might occur, precipitates might be surrounded by dislocation loops, and dislocation tangling might differ in some way from that observed in deformed, hydrogen-free vanadium. Such configurations might be retained after hydrogen removal if this could be accomplished at temperatures low enough so that dislocation motion would be unlikely. Thinned foils of such materials would not contain domain walls or other artifacts that result from concentrating the hydrogen during electrothinning.

Sheets of recrystallized vanadium and vanadium-hydrogen alloys were deformed approximately 10% in compression at a strain rate of about 10^{-5} per sec. Compression resulted in more uniform deformation than the bending used previously. They were thinned nearly to completion in the NaOH bath given in Table 78. Final thinning of a few seconds was done in the methanol-hydrochloric acid-perchloric acid bath mentioned in the publication above. The initial thinning virtually eliminated hydrogen from the alloys so the concentration effect attributed to the final bath was not encountered.

Scores of areas were photographed but no difference in dislocation configuration could be detected between vanadium and vanadium-hydrogen alloys.

TABLE 78. THE EFFECT OF THINNING VANADIUM ON ITS HYDROGEN CONCENTRATION

Thinning Technique	Fraction of Original Thickness (Approximate)	Initial Hydrogen Concentration (ppm by wt)	Final Hydrogen Concentration (ppm by wt)
Grinding (water coolant)	1/2	98	237
Grinding (methanol coolant)	3/5	4	151
Chemical 1:1:1, $\text{HNO}_3:\text{H}_2\text{SO}_4:\text{H}_2\text{O}$ $T = 313^\circ\text{K}$	1/3	101	4
Electropolish 3:1, $\text{HCl}:\text{HNO}_3$ $T = 253^\circ\text{K}$ 5-6 volts	1/2	98	207
Electropolish 10g KBr 100 ml H_2O $T = 275^\circ\text{K}$ 15 volts	?	80	7
Electropolish 10g NaOH 100 ml H_2O $T = 276^\circ\text{K}$ 5 volts	1/2	83	10

Both exhibited the same tangling and loop formation shown in Figure 188 of ANL-7155. Analysis of these loops revealed that they did not lie on primary glide planes and thus did not result from dislocations surrounding obstacles. Their orientation was such that they could have been produced by the well-known super-jog mechanism in bcc structures.

A positive result in the foregoing experiment would have shown that hydrogen does play a role in determining deformation mechanisms of vanadium at low temperatures. Unfortunately, the negative result is inconclusive, i.e., one cannot say differences did not exist before the hydrogen was removed. For example, a dislocation loop surrounding a hydride particle might collapse if the particle were transformed to metal by loss of the hydrogen.

The possibility was considered of preparing a thin foil, then charging it with hydrogen, and deforming it in the microscope while observing the behavior of the dislocations. However, surface contamination during hydrogenation was enough to spoil the foil as a microscope specimen.

A completely different approach to the problem has now been initiated. Electrical resistances of vanadium-hydrogen alloys (0 to 3.5a/oH) are being meas-

FIG. 221. Typical Plots of Electrical Resistivity vs Temperature for Vanadium-Hydrogen Alloys.

ured at temperatures between 77 and 360°K. Plots of resistivity ρ vs temperature T show a discontinuity at T_c , the critical temperature for precipitation of hydride from metal-hydrogen solid solution. Thus, one is able to develop the phase diagram at low temperatures by this method. Some typical results are shown in Figure 221. The curves have been normalized with respect to impurity differences in the samples. The appropriateness of the normalizing procedure is demonstrated by the fact that it causes coincidence of the plots for hydrogen-free alloys at all temperatures and coincidence for hydrogen alloys at all temperatures below T_c . Coincidence of all plots below about 150°K indicates that below that temperature, hydrogen is virtually insoluble in vanadium. In the interest of neatness, individual data points are not shown on the plots. It can be stated, however, that the curves for 16 alloys represent over 600 points, not one of which deviates more than 0.5% from its curve.

The resistivity one measures for an alloy is the same whether it is slow-cooled or quenched to a given temperature. Samples have been quenched from ambient temperature in liquid helium, in liquid nitrogen, and in Freon 12 at 120°K without changing the resistivity from that measured after slow-cooling. Thus, equilibrium must be attained very rapidly; the hydride particles must be very finely dispersed to eliminate the necessity for diffusion of hydrogen over great distances. This could explain why we were not able to resolve precipitates by low-temperature transmission electron microscopy.

With knowledge of the solubility of hydrogen in vanadium we can obtain the heat of solution ΔH_s of vanadium hydride in saturated vanadium-hydrogen solid solution from the relation

$$\frac{d \ln N}{d \left(\frac{1}{T} \right)} = \frac{-\Delta H_s}{R},$$

where N is the solubility limit (expressed as atomic percent) at temperature T and R is the gas constant. We have plotted the hydrogen concentration of our samples vs T_c (Figure 222) and find

$$\ln N = (5.811 \pm 0.009) - \frac{2,932 \pm 43}{RT} \quad (1)$$

Thus, $\Delta H_s = 2.932 \pm 0.043$ kcal/g atom. Veleckis⁽²⁵⁸⁾ has found that the partial molar heat of solution of hydrogen in vanadium $\overline{\Delta H}$ is -13.868 ± 0.080 kcal/mol. From these two thermodynamic quantities we can calculate the heat of formation of vanadium hydride from the saturated solid solution.⁽²⁵⁹⁾

$$\Delta H_0 = \overline{\Delta H} - 2\Delta H_s \cong -19.7 \text{ kcal/mol.}$$

The plot in Figure 222 can be extrapolated to obtain information about equilibria at lower temperatures. For example, the hydride would begin to precipitate at about 167°K in an alloy containing

⁽²⁵⁸⁾ Veleckis, Ewald, *The Thermodynamic Properties of Systems Nb-H, V-H and Te-H*, Thesis, Illinois Institute of Technology, 1960.

⁽²⁵⁹⁾ Peterson, D. T., and Westlake, D. G., *Trans. Met. Soc. AIME* **215**, 444 (1959).

0.05 *a/o* H (10 ppm H by wt). At 150°K, where one can no longer distinguish hydrogen-free metal from metal-hydrogen alloys, the solubility limit is 0.018 *a/o* (3.6 ppm).

One can also plot the information given in Figure 221 in the usual form of a phase diagram (Figure 223). Our diagram does not agree with the one Veleckis proposed. However, his is not based on experimental measurements in this temperature range. He obtained his by measuring equilibrium hydrogen pressures over the various vanadium-hydrogen alloys at considerably higher temperatures and extrapolating his results to the temperature range of interest here.

The plots of ρ vs T in Figure 221 are parallel at the highest temperatures, i.e. when all hydrogen is in solid solution. The increment in resistivity $\Delta\rho$ is proportional to the amount of hydrogen in solution (Figure 224).

$$\Delta\rho = 1.14 \mu\Omega\text{cm per } a/o \text{ hydrogen}$$

Precise values of hydrogen embrittlement temperatures must be obtained before one can say definitely that there is a correlation between them and our

46160

FIG. 222. Log Hydrogen Solubility vs Reciprocal Absolute Temperature for Vanadium Hydrogen Alloys.

46157

FIG. 223. Solvus for Vanadium-rich Vanadium-Hydrogen Alloys.

46158

FIG. 224. Increase in Electrical Resistivity vs Concentration of Hydrogen in Solid Solution.

values of T_c . The limited information available, however, indicates a correlation probably exists, thereby suggesting that hydrogen embrittlement of vanadium results from hydride precipitation, just as it does for zirconium.^(260,261)

A similar study of ρ vs T for niobium-hydrogen alloys is planned and the technique will also be used to study the effect of stress on metal-hydrogen phase equilibria at low temperatures.

⁽²⁶⁰⁾ Westlake, D. G., *Acta Met.* **12**, 1373-1380 (1964).

⁽²⁶¹⁾ Westlake, D. G., *Trans. Met. Soc. AIME* **233**, 368-372 (1965).

D. TRANSFORMATIONS

1. Role of the Structure of Dislocations in the hcp $\rightarrow$ bcc Diffusionless Transformation

(E. S. FISHER AND L. C. R. ALFRED)

a. RELATIONSHIP TO ELASTIC ANISOTROPY

Elastic anisotropy is known to be closely associated with the occurrence of diffusionless phase transformation.⁽²⁶²⁾ The calculations of deWit and Koehler⁽²⁶³⁾ and, more recently, of Head⁽²⁶⁴⁾ have suggested that the elastic stress fields around dislocations may be responsible for the mechanisms of the transformations from bcc structures. Their work shows that within the assumptions of Eshelby's elastic continuum model,⁽²⁶⁵⁾ straight dislocations lying in certain specific crystallographic directions are not stable, because of negative line tensions. The exact role of the crooked or curved dislocations is not understood; nevertheless, these results offer a reasonable explanation for the apparently consistent relationship between elastic anisotropy in hcp metals and the hcp $\rightarrow$ bcc transformation. The group of hcp metals that have this transformation also have a positive temperature dependence of $A = c_{44}/c_{66}$.⁽²⁶⁶⁾ On the other hand, in the hcp metals that do not have this transformation A has a negative or zero temperature coefficient. The calculations described in this report were undertaken to determine whether the elastic anisotropy observed in hcp metals can produce anomalous properties of dislocations, such as the negative line tensions found in bcc metals.

In the mathematical theory⁽²⁶⁵⁾ of the stress fields produced by a dislocation in an elastic continuum the self-energy of a dislocation outside of the dislocation core is given as

$$E = \frac{Kb^2}{4\pi} \ln \frac{R}{r_0} \quad (1)$$

where b is the magnitude of the Burgers vector, R is the outer radius of the stress field, r_0 is the core diameter and K is the elasticity factor relating the stress components to the displacements produced by the dislocation. K is a function of the single-crystal elastic moduli, the Burgers vector, the crystal orientation of

the dislocation line, and the plane within which the dislocation moves. Within the approximation of the anisotropic elastic continuum model K is the important factor for calculating the width of an unextended dislocation, the line energy and the relative widths of stacking faults (for a given stacking fault energy).

The metals considered and information pertinent to this survey are listed in Table 79. In the last Annual Report (ANL-7155) we presented the results of a survey of K factors for dislocations with $b = \langle a \rangle$, or $\frac{1}{3} \langle 11\bar{2}0 \rangle$. This survey has since been extended to dislocations with $b = \langle a + c \rangle$, or $\frac{1}{3} \langle 11\bar{2}3 \rangle$ and $b = \langle c \rangle$, or $\langle 0001 \rangle$. We have, in addition, included some metals and temperatures not previously considered. Most of these calculations were computed numerically from a machine program. For some orientations the K values can be computed from analytical expressions; the results for the metals not previously considered are primarily from this category.

b. RESULTS

(1) K Factors for Screw Dislocations, K_s

The K_s values are summarized in Table 80. K_s for $b = \langle a \rangle$ and $b = \langle c \rangle$ are computed analytically from

$$K_s \langle a \rangle = \sqrt{c_{44}c_{66}} = \frac{c_{44}}{A^{1/2}} \quad (2)$$

and

$$K_s \langle c \rangle = c_{44} \quad (3)$$

$K_s \langle a \rangle$ is generally larger than $K_s \langle c \rangle$ for the Group I metals, whereas the reverse is true for Group II. The relative values of $K_s \langle a + c \rangle$ are not clearly related to A . $K_s \langle a + c \rangle$ is generally larger than $K_s \langle a \rangle$ or $K_s \langle c \rangle$. Gross exceptions are, however, evident for Cd and Zn where $K_s \langle a \rangle$ have the largest values at all temperatures. On the other hand, Dy, Y and Be are surprisingly close to isotropic considering the relatively large deviations from the ideal c/a ratio.

(2) K Factors for Edge Dislocations, K_e

For anisotropic materials the K factor for an edge dislocation with a given b will depend on the plane in which the displacement occurs. Table 81 lists some of the calculated K_e values. For $b = \langle a \rangle$, the K_e values

⁽²⁶²⁾ Zener, C., *Elasticity and Plasticity of Metals* (University of Chicago Press, Chicago, 1948).

⁽²⁶³⁾ deWit, G., and Koehler, J. S., Phys. Rev. **116**, 1113 (1959).

⁽²⁶⁴⁾ Head, A. K., Phys. Stat. Sol. **19**, 185 (1967).

⁽²⁶⁵⁾ Eshelby, J. D., Phil. Mag. **40**, 903 (1949).

⁽²⁶⁶⁾ Fisher, E. S., and Dever, D., Trans. AIME **239**, 48 (1967).

were computed for the basal and prism planes as well as for the planes inclined 30° , 45° and 60° to the basal planes. Table 81 lists only the 60° planes, since the $\{11\bar{2}2\}$ and $\{10\bar{1}1\}$ type planes would lie close to the 60° orientation. The variation of $K_e \langle a \rangle$ with glide plane is clearly associated with the shear modulus anisotropy; for $A < 1$, K_e generally increases with deviation from the basal plane and the reverse correspondence is true for $A > 1$. Magnesium, rhenium and ruthenium are slightly exceptional in this correlation.

For $b = \langle a + c \rangle$ and $b = \langle c \rangle$ we considered only the glide planes that have been observed as active slip planes. The differences in K_e between $\{11\bar{2}3\}$ and $\{10\bar{1}1\}$ type planes are very small. The relative values of K_e for the different Burgers vectors are, however, quite marked for cadmium and zinc, where the K_e for $b = \langle a \rangle$ are considerably greater than for the other

TABLE 79. $A = c_{44}/c_{66}$ AND hcp $\rightarrow$ bcc TRANSFORMATION TEMPERATURES FOR hcp METALS

Metal	Temp Range of Measurements ($^\circ\text{K}$)	A at Highest Temp	Temp of hcp $\rightarrow$ bcc Transformation ($^\circ\text{K}$)	Ref. to Elastic Moduli
Group I				
Cd	4-575	0.521	—	$\begin{cases} 267 \\ 268 \end{cases}$
Zn	4-670	0.573	—	269
Co	4-523	1.046	—	266
Mg	4-300	0.971	—	270
Re	4-1123	0.976	—	266
Ru	4-923	0.923	—	266
Group II				
Tl	4-300	2.688	507	271
Zr	4-1123	2.000	1135	272
Ti	4-1156	2.91	1155	272
Hf	4-598	1.149	~ 2000	272
Dy	4-923	1.126	1670	266
Y	4-898	1.129	1760	273
Er	4-300	1.006	1600	266
Be	4-300	1.223	1523	274

(267) Garland, C. W., and Silverman, J., Phys. Rev. **119**, 1218 (1960).

(268) Chang, Y. A., and Himmel, L., J. Appl. Phys. **37**, 3787 (1966).

(269) Alers, G. A., and Neighbours, J. R., J. Phys. Chem. Solids **7**, 58 (1958).

(270) Slutsky, L. J., and Garland, C. W., Phys. Rev. **107**, 972 (1957).

(271) Ferris, R. W., Shepard, M. L., and Smith, J. F., J. Appl. Phys. **34**, 768 (1963).

(272) Fisher, E. S., and Renken, C. J., Phys. Rev. **135**, A482 (1964).

(273) Smith, J. F., and Gjevne, J. A., J. Appl. Phys. **31**, 645 (1960).

(274) Smith, J. F., and Arborgast, C. L., J. Appl. Phys. **31**, 99 (1960).

TABLE 80. SUMMARY OF K FACTORS FOR SCREW DISLOCATIONS WITH DIFFERENT BURGERS VECTORS

Metal	Temp ($^\circ\text{K}$)	$K_s \times 10^{-12}$ dynes/cm 2		
		$b = \langle a \rangle$	$b = \langle c \rangle$	$b = \langle a + c \rangle$
Cd	300	0.277	0.203	0.217
Cd	575	0.165	0.119	0.129
Zn	300	0.497	0.388	0.368
Zn	670	0.352	0.267	0.261
Co	300	0.729	0.753	0.879
Co	523	0.660	0.675	0.803
Mg	300	0.167	0.184	0.177
Re	300	1.659	1.606	1.845
Re	923	1.410	1.391	1.573
Ru	300	1.852	1.806	1.954
Ru	923	1.607	1.534	1.696
Zr	300	0.336	0.320	0.372
Zr	1133	0.150	0.212	0.207
Ti	300	0.405	0.467	0.461
Ti	1155	0.171	0.291	0.245
Hf	300	0.538	0.557	0.573
Hf	598	0.467	0.501	
Dy	300	0.243	0.243	0.253
Dy	698	0.207	0.213	0.223
Y	300	0.247	0.249	0.260
Y	898	0.195	0.207	
Be	300	1.469	1.528	1.525

TABLE 81. SUMMARY OF K FACTORS FOR EDGE DISLOCATIONS

Metal	Temp ($^\circ\text{K}$)	$K_e \times 10^{-12}$ dynes/cm 2					
		$b = \langle a \rangle$			$b = \langle a + c \rangle$	$b = \langle c \rangle$	
		Basal	60°	$\{hk\cdot 0\}$	$\{11\bar{2}2\}$	$\{10\bar{1}1\}$	$\{hk\cdot 0\}$
Cd	300	0.354	0.470	0.508	0.269	0.277	0.236
Cd	575	0.218	0.303	0.334	0.178	0.180	0.157
Zn	300	0.555	0.727	0.778	0.405	0.423	0.346
Zn	670	0.415	0.561	0.607	0.310	0.323	0.269
Co	300	1.244	1.101	1.087	1.298	1.293	1.344
Co	523	1.153	1.017	1.004	1.202	1.195	1.244
Mg	300	0.247	0.241	0.242	0.250	0.248	0.251
Re	300	2.547	2.467	2.477	2.641	2.612	2.677
Re	923	2.242	2.134	2.130	2.328	2.303	2.362
Ru	300	2.534	2.509	2.517	2.631	2.616	2.669
Ru	923	2.261	2.260	2.277	2.335	2.321	2.364
Zr	300	0.540	0.528	0.532	0.567	0.562	0.578
Zr	1133	0.352	0.224	0.200	0.387	0.375	0.409
Ti	300	0.676	0.575	0.551	0.703	0.694	0.714
Ti	1155	0.446	0.224	0.183	0.485	0.467	0.501
Hf	300	0.785	0.749	0.742	0.809	0.804	0.818
Y	300	0.347	0.336	0.336	0.342	0.342	0.345
Dy	300	0.333	0.328	0.328	0.338	0.338	0.342
Dy	698	0.299	0.285	0.251	0.307	0.307	0.313
Be	300	1.543	1.478	1.449	1.623	1.624	1.655
Er	300	0.386		0.378	0.400	0.321	0.384

cases. For the other metals considered, the K_e for $b = \langle a \rangle$ are either the smallest or there exists little variation in K_e .

(3) *K* Factor for Mixed Dislocations

When the angle between the Burgers vector and the dislocation line is neither 0° or 90° the *K* factor is generally intermediate in value to K_e and K_s . If the plane containing the two directions, i.e. the glide plane, is elastically isotropic

$$K(\alpha) = K_s \cos^2 \alpha + K_e \sin^2 \alpha \quad (4)$$

where α is the angle between the two directions. This relation holds only for the basal planes. In those cases where *A* is near unity Equation (4) has been found to give errors less than 2% from the numerical calculations. Tables 79 and 80 and Equation 4 can, then, be used for obtaining reasonable approximations of *K* at any angle α within the planes noted for most of the hcp metals. Rather large errors are, however, encountered for cadmium and zinc at all temperatures and for titanium and zirconium at temperatures above 700°K . For titanium at temperatures above 1100°K , for example, *K* within the prism planes has a pronounced maximum at $\alpha = 60^\circ$, for $b = \langle a \rangle$.

(4) Line Tension on a Bowed Dislocation

If we neglect the energy of a dislocation core and the interaction between the bowed and straight parts of a dislocation line, the effective line tension against deformation can be given by

$$T = E + \frac{\partial^2 E}{\partial \alpha^2} = \frac{b^2}{4\pi} \left(\ln \frac{R}{r_0} \right) \left(K + \frac{\partial^2 K}{\partial \alpha^2} \right) \quad (5)$$

where *R* and r_0 are as defined in Equation (1) and are assumed invariant with α .⁽²⁶³⁾ The variation of *T* with the elastic moduli can then be computed from the variation of *K*(α). The general procedure for computing *T* was to (1) compute *K* at 15° intervals of α within a given plane, (2) fit the numerical results to a polynomial of the form

$$K(\alpha) = \sum_{n=0}^5 A_n \cos 2n\alpha + B_n \sin 2n\alpha \quad (6)$$

and (3) evaluate *K* and $\partial^2 K / \partial \alpha^2$. For the basal plane Equation (4) is used to obtain an analytical expression for *T* (given in ANL-7155).

The prime reason for the study of line tensions was to see whether the line tensions become negative at temperatures approaching phase transformations, as was shown to be the case for bcc lithium at 77°K .⁽²⁶³⁾ The results of this study for dislocations in the basal plane with $b = \langle a \rangle$, were described in ANL-7155, where it was shown from the analytical equation that negative line tensions do in fact exist in titanium and zirconium at temperatures above 750°K . This arises from the fact that the Poisson's ratios within the basal planes, $-(s_{12}/s_{11})$, become greater than $1/2$.

The results of the numerical calculations of *T* have revealed several other dislocation orientations that have negative line tensions in titanium and zirconium above 900°K : (1) $b = \langle a \rangle$ in planes inclined 45° to the basal plane, (2) $b = \langle c \rangle$ in the prismatic planes and (3) $b = \langle a + c \rangle$ in $\{11\bar{2}2\}$ and/or $\{10\bar{1}1\}$ planes. These results are not associated with abnormal Poisson's ratios but arise from the coefficients of the polynomials fitted to the numerical data. The interpolation between calculated points may give rise to erroneously large negative curvatures. It seems, however, that since the negative *T*'s are observed only in titanium and zirconium they are associated with *A* being larger than 1.5.

(5) Repulsive Forces between Partial Dislocations

When the elastic force between partial dislocations is computed in terms of the *K* factor and equated to the stacking fault energy, γ , we find

$$F = \gamma = M \frac{b}{d}$$

where *M* is a function including the appropriate *K* factor, *b* is the magnitude of the Burgers vectors and *d* is the distance between partials or width of the stacking fault. In the last Annual Report we presented the results for stacking faults bounded by Shockley partial dislocations moving in the basal planes. For all the cases considered, *M* decreases with increasing temperature, thus suggesting that *d* would decrease with increasing temperature if γ remains temperature independent. In fact *M* becomes very near zero for split screw dislocations in the basal planes of titanium and zirconium at the respective temperatures of structural transformation.

The only other possible splitting that we have investigated is that of the $b = \langle a + c \rangle$ splitting into two $b = \langle p + \frac{1}{2}c \rangle$ partials (*p* is the notation for a $\frac{1}{3}\langle 10\bar{1}0 \rangle$ vector) or $\{11\bar{2}2\}$ planes. Here, again, the repulsive forces remain positive but decrease with increasing temperature. It thus appears that the hcp $\rightarrow$ bcc transformation is not associated with temperature induced growth of stacking faults within the hcp structure.

(6) Widths of Unextended Dislocations

When the analyses of Eshelby⁽²⁶⁵⁾ and of Bullough and Bilby⁽²⁷⁵⁾ are used to evaluate the range of distortion within the core of the dislocation, the widths of an edge and a screw dislocation are, respectively

$$r_0 = K_e a_0 / c'_{66} \\ r_0 = K_s a_0 / c'_{44}$$

⁽²⁷⁵⁾ Bullough, A., and Bilby, B. A., Proc. Phys. Soc. (London) **B67**, 615 (1954).

where r_0 is the radius of the dislocation core, a_0 is the glide separation and c'_{66} and c'_{44} are shear moduli associated with the shear displacements produced by a moving dislocation. For a stationary dislocation in an isotropic medium with Poisson's ratio of $1/3$ the widths of the edge and screw are $3/2 a_0$ and a_0 , respectively.

This analysis suggests that the exterior shape of the core of the screw dislocation with $b = \langle a \rangle$ in hcp metals will depend on the anisotropy factor A . The radius of the core in a direction perpendicular to the c -axis will be inversely proportional to $A^{1/2}$, whereas the radius in the c -direction will be directly proportional to $A^{1/2}$. Thus, as was shown in ANL-7155, positive temperature dependence of A implies a spreading of the screw dislocation core within prism planes and a shrinkage within the basal planes. In titanium, for example, the core is essentially circular in shape at 4°K but at 1155°K, i.e. the hcp $\rightarrow$ bcc transformation temperature, the radius along the c -axis is about 3 times that in the basal plane.

The widths of edge dislocations with $b = \langle a \rangle$ are not directly associated with the shear anisotropy and are generally temperature independent (less than 10% change) within the ranges for which elastic moduli measurements are available. For titanium and zirconium, however, the widths of edge dislocations within the prism planes increase about 20% from 4°K to the respective transformation temperatures.

Among the new cases considered, i.e. $b = \langle a + c \rangle$ and $b = \langle c \rangle$ we have not found any marked effects of temperature on the dislocation widths. It thus appears that the effects of temperature on the shape of the dislocation core are significant only for $b = \langle a \rangle$.

⁽²⁷⁶⁾ Burger, W. G., *Physica* **1**, 561 (1934).

c. CONCLUSIONS

In regard to the original purpose of this investigation, there are two effects of temperature on dislocation properties that seem to be associated with the thermally induced hcp $\rightarrow$ bcc transformation:

- (1) Negative line tensions occur for several dislocation geometries in titanium and zirconium at temperatures above 700°K.
- (2) The cores of screw dislocations with $b = \langle a \rangle$ become distorted from circular to ellipsoidal shape as the anisotropy ratio, $A = c_{44}/c_{66}$, increases.

No obvious explanation is suggested for the association of negative line tensions and martensitic phase transformations. Phenomenologically the correlation suggests that straight dislocations undergo an abrupt collapse to a sharply bent or curved line as the temperature approaches that which is the observed transformation temperature.⁽²⁶⁴⁾

The second observation is clearly associated with W. G. Burger's⁽²⁷⁶⁾ model for the overall deformation that accounts for the hcp $\rightarrow$ bcc transition. Accordingly one would expect the dislocations with $b = \langle a \rangle$ and moving in the prism planes to be the primary means of achieving the transformation shear. An abnormally large dislocation width would imply an abnormally small Peirls-Nabarro frictional force for moving such dislocations within the prism planes. An alternative interpretation is that the elliptical cross-sections of the screw dislocations produce the nuclei for the bcc phase. It appears, then, that the correlation between the temperature dependence of the elastic moduli and the occurrence of the hcp $\rightarrow$ bcc transformation may perhaps be explained on the basis of the dislocation width concept.

2. Effects of Magnetic Transitions on Elastic Properties (E. S. FISHER AND D. DEVER)

a. INTRODUCTION

The effects of phase transformations on the single-crystal elastic moduli can in principle be useful in understanding the difference between the phases as well as the mechanisms of the transformations. For example, the paramagnetic-to-ferromagnetic transformation of nickel merely produces an intrinsic increase in the temperature dependence of the elastic moduli through the onset of the direct exchange interaction between electrons.⁽²⁷⁷⁾ At zero magnetic field

two additional effects are observed in nickel that are associated with the stress-induced movement of magnetic domain walls, the ΔE effect, and rotation of the magnetic vectors. The latter two effects give rise to acoustic attenuation as well as a lowering of elastic constants. The antiferromagnetic transformations in chromium produce a different effect: the curves of elastic moduli versus temperature show a sharp drop over a few degrees above the transition and a sharp increase, leaving an inverted cusp to define the transition temperature.⁽²⁷⁸⁾ These effects are again produced

⁽²⁷⁷⁾ Alers, G. A., Neighbours, J. L., and Sato, H., *J. Phys. Chem. Solids* **13**, 40 (1960).

⁽²⁷⁸⁾ Bolef, D. I., and de Klerk, J., *Phys. Rev.* **129**, 1063 (1963).

46216

FIG. 225. Variation with Temperature Below 300°K of the Principal Elastic Stiffness Moduli of Gd.

by the direct exchange mechanism, but apparently contain contributions from a slight change in crystal symmetry.

Alpha uranium displays evidence of a transformation between 41°K and 43°K, the nature of which has not been established.⁽²⁷⁹⁾ All elastic moduli have a temperature dependence that produces the inverted cusp effect as in chromium. One of the moduli, however, reaches a maximum at 200°K above the transition and decreases by at least a factor of three over the 200°K temperature range. The transformation also produces a very pronounced acoustic attenuation for this mode as well as certain shear modes. These effects resemble somewhat the ferroelectric transition in strontium titanate⁽²⁸⁰⁾ or order-disorder transition in NH_4Cl ,⁽²⁸¹⁾

⁽²⁷⁹⁾ Fisher, E. S., and McSkimin, H. J., *Phys. Rev.* **124**, 67 (1961).

⁽²⁸⁰⁾ Bell, R. O., and Rupprecht, G., Technical Memo. T-396, Raytheon Co., July 26 (1962).

⁽²⁸¹⁾ Garland, C. W., and Renard, R., *J. Chem. Phys.* **44**, 1130 (1966).

neither of which could be occurring in pure uranium. One possible explanation was that the 43°K transition may be in some way related to the indirect exchange effects that produce the magnetic structures in the rare earth metals. The effects of these transitions on the single-crystal elastic moduli have not so far been observed. A cursory study of these effects in certain rare earth metals is in progress.

During the past year measurements of the elastic moduli in erbium and gadolinium have been completed in the range of 2° to 300°K. The measurements of dysprosium are not complete in this range because of coupling breakage at the antiferromagnetic to ferromagnetic transition.

b. GADOLINIUM

The most recent single-crystal magnetization measurements give T_c for gadolinium at $293^\circ \pm 0.5^\circ\text{K}$.⁽²⁸²⁾ Between 293° to 248°K the moments are aligned parallel to the c -axis. The moments begin to deviate from the c -axis between 248° and 195°K, where a maximum deviation is attained.^(283,284) One reference⁽²⁸⁴⁾ gives 220°K as the temperature at which the maximum deviation is attained. This deviation then decreases gradually as the temperature is lowered. The variations of the principal elastic moduli below 300°K are given in Figure 225. By far the largest effect of ordering is observed in c_{33} , the modulus for compressing the c -axis. This modulus passes through a maximum at 330°K and then drops sharply as the temperature approaches T_c , which we find at 286°K. The effects on the other moduli are relatively small.

At lower temperatures c_{33} increases smoothly but sharply to 225°K, at which point there is another anomaly accompanied by a large acoustic attenuation. Normal behavior returns at 200°K. Between 200° and 2°K there are, however, some abnormal changes in slope that may indicate further abrupt changes in the directions of the aligned moments at 190° and 50°K.

The shift in moment direction at 225°K has no significant effects on the other elastic moduli, thus confirming that no further phase transitions occur below 286°K. (It was at one time proposed that a phase change occurs at 210°K.⁽²⁸⁵⁾)

The Debye temperature of gadolinium computed from the 2°K moduli is 181.5°K. The significance of this value in relation to specific heat measurements of rare earths is discussed below.

⁽²⁸²⁾ Graham, C. D., Jr., *J. Appl. Phys.* **36**, 1135 (1963).

⁽²⁸³⁾ Graham, C. D., Jr., *J. Phys. Soc. Japan* **17**, 1310 (1962).

⁽²⁸⁴⁾ Corner, W. D., Roe, W. C., and Taylor, K. N. R., *Proc. Phys. Soc.* **80**, 927 (1962).

⁽²⁸⁵⁾ Belov, K. P., et al., *Soviet Phys. JETP* **13**, 1096 (1961).

FIG. 226. Effects of the Magnetic Phase Transitions on the Principal Elastic Moduli of Dy.

c. DYSPROSIUM

Dysprosium becomes antiferromagnetically ordered upon cooling below 179°K, according to neutron diffraction measurements.⁽²⁸⁶⁾ The moments lie in the basal planes but the direction rotates about the *c*-axis on adjacent basal planes, giving a screw or helical structure. The angular deviation between adjacent moments decreases with temperature to 85°K, at which point there is a transition to a ferromagnetic structure with all moments parallel to [1120]. This gives rise to a magnetostrictive distortion in the lattice constants and an orthorhombic unit cell below 85°K.

The variations in the elastic moduli below 500°K are given in Figure 226 (see ANL-7155 for higher temperature data). As in the case of gadolinium, the c_{33} modulus is the most affected by the ordering and the Néel temperature, T_N , is preceded upon cooling by a maximum in c_{33} at 250°K. Our data indicate T_N at 176°K. The rotation of the magnetic moments with decreasing temperature causes a marked increase in c_{33} and c_{44} , the modulus corresponding to basal plane shear. Within the basal planes, however, the longitudinal stiffness, c_{11} , and the distortional stiffness, c_{66} , begin to decrease sharply as the screw angle de-

creases. The transformation to ferromagnetic alignment causes an abrupt change in *c/a* ratios and a coupling breakage that prevents further measurements of c_{11} and c_{66} .

The abrupt increases in c_{33} and c_{44} occur at 83° and 85°K respectively. However, c_{44} then decreases abruptly at 80°K, suggesting a two-stage process for the ferromagnetic transition. The X-ray diffraction measurements of Darnell and Moore⁽²⁸⁷⁾ indicate that a decrease in crystallographic symmetry about the *c*-axis occurs at 86°K. This change implies that the velocity of a shear wave propagated along the *c*-axis should have a dependence on the direction of displacement within the (0001) plane. We have checked this point carefully by rotating the displacement direction in 30° intervals of arc and have found no significant deviation from the sixfold symmetry of the hexagonal cell.

d. ERBIUM

Erbium has three different magnetically ordered phases at zero magnetic field.⁽²⁸⁸⁾ Neutron-diffraction data place the paramagnetic transition at 80°K.⁽²⁸⁸⁾

⁽²⁸⁷⁾ Darnell, F. J., and Moore, E. P., J. Appl. Phys. **34**, 1337 (1963).

⁽²⁸⁸⁾ Coble, J. W., Wollan, E. O., Koehler, W. C., and Wilkinson, M. K., J. Appl. Phys. **32**, 495 (1961).

⁽²⁸⁶⁾ Wilkinson, M. K., Koehler, W. C., Wollan, E. O., and Coble, J. W., J. Appl. Phys. **32**, 485 (1961).

46220

FIG. 227. Effects of the Magnetic Phase Transitions on the Principal Elastic Moduli of Er.

Between 80° and 52°K the moments are parallel to the c -axis but modulated sinusoidally in magnitude, with a period of 3.5 lattice constants. Between 52° and 20°K a complex helical distribution of moments exists and at 20°K the moments along the c -axis become ferromagnetically ordered but a smaller perpendicular component still exists in a helical arrangement. The transition temperatures indicated by the elastic modulus data (Figure 227) agree with the above data. The c_{11} , c_{66} and c_{44} curves have a sharp increase in slope at 80°K. c_{33} has a maximum at 20°K above the transition and reversal in slope at 80°K; as in gadolinium and dysprosium, T_N is preceded on cooling by a softening of the c_{33} mode. c_{11} and c_{66} attained maximum values at $53 \pm 1^\circ$ and then decrease sharply as the helical ordering sets in. c_{44} and c_{33} , however, begin to decrease at 60° and 57°K, respectively, and their curves pass smoothly through 53°K. The change in antiferromagnetic arrangement has a very large effect on c_{33} and c_{44} and produces a large acoustic attenuation of the c_{11} and c_{66} modes. This attenuation decreases sharply at the ferromagnetic transition at 20°K.

The c_{33} and c_{44} curves both show a significant hysteresis effect at the ferromagnetic transition. The c_{33} transition is increased about 2°K on warming. The c_{44} transition occurs at 20°K on cooling and 21°K during warming.

The Debye temperature of Er computed from the 2°K moduli is 191°K.

e. DISCUSSION OF RESULTS

The above data clearly show that the elastic moduli are very significantly affected by the ordering and anisotropy of magnetic moments in the rare earth metals. It is important to emphasize, however, that these measurements were carried out in the absence of an external magnetic field and, consequently, could be subject to the effects of stress-induced domain wall movement. Since our results generally show an enhancement in the elastic moduli upon cooling from the paramagnetic state, it would appear that these effects are not significant.

The results for gadolinium show clearly several of the characteristics that are found in all three of the metals investigated:

- (1) c_{33} is the modulus most affected by the transformations and is clearly affected by the electron interactions at temperatures considerably within the paramagnetic phase,
- (2) some of the moduli do not show a decrease at the transition but merely change by an enhancement of the temperature dependence,
- (3) the transformations are not accompanied by large acoustic attenuation; changes in the directions of the already aligned moments do, how-

ever, involve attenuation that may be associated with a ΔE effect.

These characteristics have only one factor in common with the low-temperature transformations in α -uranium; c_{11} of α -uranium has a maximum at temperatures well above phase transition temperature.⁽²⁷⁹⁾ Other than this common factor, the low-temperature transitions in α -uranium do not fit the characteristics noted, i.e. the elastic moduli of α -uranium are decreased upon cooling through the transitions and a very large acoustic attenuation is encountered at the transition temperatures. It thus appears that the transitions in α -uranium are not related to ordering of magnetic moments.

The Debye temperatures computed from the 4°K elastic moduli of gadolinium and erbium are of considerable value in the interpretation of the heat-capacity data of the rare earth metals. Because of the magnetic contribution to the low-temperature specific heats the conventional method of deducing Debye temperatures cannot be applied without ambiguity, since the magnetic contributions may also vary with T^n , where n is near 3.⁽²⁸⁹⁾ In order to deduce the actual

value of n , which is of great interest to the theory of the interaction of the 4f electron spins, one must make some assumption with regard to the Debye temperature.

One procedure for arriving at a Debye θ in the absence of the elastic moduli data is to assume that all the heavy rare earths have about the same lattice specific heat as lutetium.⁽²⁸⁹⁾ Since lutetium has no magnetic contribution the Debye θ of lutetium can be derived from specific heat measurements without ambiguity. This method gives the Debye θ of gadolinium and erbium as 210°K, compared to 181°K and 191°K respectively from our data. The other method, proposed earlier by Lounasmaa,⁽²⁹⁰⁾ is to assume that the Debye θ increases linearly with atomic number between lanthanum and lutetium. With the Debye θ 's of lanthanum and lutetium determined from specific heat data, this method gives Debye θ 's for gadolinium and erbium of 176° and 195°K, respectively. The agreement with our elastic moduli data are quite satisfactory in this latter case. It thus appears that the interpolation method is a reasonably accurate means of estimating the lattice specific heats of the rare earth metals.

⁽²⁸⁹⁾ Lounasmaa, O. V., and Sundstrom, L. J., Phys. Rev. **150**, 399 (1966).

⁽²⁹⁰⁾ Lounasmaa, O. V., Phys. Rev. **133**, A222 (1964).

E. DIFFUSION IN METALS

1. Isotope Effect Studies (S. ROTHMAN AND N. PETERSON)

The object of this program is to study the details of the elementary diffusional processes by means of measurements of the dependence of the diffusion coefficient on the mass of the diffusing isotope (the isotope effect). The isotope effect has been measured for the diffusion of zinc in silver, copper, ordered and disordered CuZn, and zinc.

The isotope effect is connected with the correlation factor for tracer diffusion, f , by^(291,292)

$$f\Delta K = E = \frac{\frac{D^\alpha}{D^\beta} - 1}{\left(\frac{m^\beta}{m^\alpha}\right)^{1/2} - 1}. \quad (1)$$

Here E is defined as the strength of the isotope effect, D^α and m^α are respectively the diffusion coefficient and mass of isotope α , and ΔK is a correction term for the deviation of the atomic vibration frequency, ν , from proportionality to the reciprocal of the square root of the atomic mass, the deviation being due to many-body effects at the saddle point. ΔK also has a physical meaning;^(292,293) it is the fraction of the kinetic energy of the saddle-point configuration, associated with motion in the direction of diffusion, that is possessed by the diffusing atom. (For a harmonic crystal $\nu \propto m^{-1/2}$ and $\Delta K = 1$.)

The correlation factor, f , is a measure of the non-randomness of diffusion; diffusion is nonrandom when it takes place via the vacancy mechanism. (It is a safe assumption that diffusion in the above materials takes place via single vacancies.) For self-diffusion, f is a number that can be calculated, given the lattice structure and the diffusion mechanism. Thus a measurement of the isotope effect for self-diffusion yields a value of ΔK . (Such a measurement has been made for silver,⁽²⁹⁴⁾ and the result, $\Delta K = 0.86 \pm 0.05$, has been used in our calculations.) For impurity diffusion, f is a function of the different vacancy jump frequencies, w_i , near the impurity (Figure 228). For an fcc lattice the simplest form of f which neglects returning vacancies, is:⁽²⁹⁵⁾

$$f = \frac{w_1 + 7/2 w_3}{w_1 + w_2 + 7/2 w_3}. \quad (2)$$

If returning vacancies are considered,⁽²⁹⁶⁾

$$f = \frac{w_1 + 7/2 F w_3}{w_1 + w_2 + 7/2 F w_3}, \quad (3)$$

where F is a function only of the jump frequency ratio w_4/w_0 . All the w 's are assumed to depend exponentially on the temperature:

$$w_i = \nu_i \exp\left(-\frac{H_i}{RT}\right). \quad (4)$$

Correlation factors for the diffusion of impurities in silver and copper have been calculated theoretically⁽²⁹⁷⁾ on the basis of a model that treats the vacancy and the impurity as screened point charges. Actually, it is $\Delta H_i = H_i - H_0$ that is calculated (see Equation 4); to obtain w_1 and w_3 , it was assumed that $\nu_1 = \nu_3 = \nu_0$. (We show later that this is a bad assumption.)

The jump frequencies of Figure 229 are also the ones involved in the self-diffusion of solvent in a dilute solution. If one then takes Equation 2 for f , one obtains (Lidiard's theory)⁽²⁹⁸⁾

$$f = 1 - \frac{4 f_0}{b + 18} \left(\frac{D_i}{D_s(0)} \right) \quad (5)$$

Here f_0 is the correlation factor for self-diffusion in the pure solvent (9/11 for an fcc lattice in the approximation of Equation 2), D_i and $D_s(0)$ are the diffusion coefficients of the solute and solvent respectively in the pure solvent, and the constant b is defined by:

$$D_s(c) = D_s(0) (1 + bc). \quad (6)$$

$D_s(c)$ is the self-diffusion coefficient of the solvent in an alloy containing atomic fraction c of solute. In other words, f can be obtained from measurements of the dependence of the solvent self-diffusion coefficient on solute concentration. The theory leading to Equation 5 has recently been re-worked⁽²⁹⁹⁾ to show that given b , f , and $D_i/D_s(0)$, one can calculate the ratios w_4/w_0 , w_3/w_1 , and w_2/w_1 .

⁽²⁹¹⁾ Schoen, A. H., Phys. Rev. Letters **1**, 138 (1958).

⁽²⁹²⁾ Mullen, J. G., Phys. Rev. **121**, 1649 (1961).

⁽²⁹³⁾ LeClaire, A. D., Phil. Mag. **14**, 1271 (1966).

⁽²⁹⁴⁾ Peterson, N. L., and Barr, L. W. To be published.

⁽²⁹⁵⁾ LeClaire, A. D., and Lidiard, A. B., Phil. Mag. **1**, 518 (1956).

⁽²⁹⁶⁾ Manning, J. R., Phys. Rev. **128**, 2169 (1962).

⁽²⁹⁷⁾ LeClaire, A. D., Phil. Mag. **7**, 141 (1962).

⁽²⁹⁸⁾ Lidiard, A. B., Phil. Mag. **5**, 1171 (1960).

⁽²⁹⁹⁾ Howard, R. E., and Manning, J. R., To be published in Phys. Rev.

We have obtained the following experimental results:
Silver: b , $D_i/D_s(0)$, and E (and hence f) have been measured, and values of w_4/w_0 , w_3/w_1 , and w_2/w_1 have been obtained.

- IMPURITY ATOM
- ⊙ SOLVENT ATOM
- VACANCY

46214

FIG. 228. Vacancy Jump Frequencies near an Impurity in an fcc Lattice.

Copper: E has been measured and values of f have been deduced from it.

CuZn: E has been measured for the disordered and ordered ($S = 0.7$) alloy, and qualitative conclusions about the diffusion mechanism have been reached.

Zinc: E has been measured and ΔK has been obtained from it.

Experimental Techniques: The experimental techniques for the isotope effect measurements were given in last year's Annual Report (ANL-7155). Standard techniques⁽³⁰⁰⁾ were used for the measurements of b . All specimens were single crystals except the Ag-Zn alloys, which had grain diameters of several millimeters. All given temperatures are accurate to $\pm 1^\circ\text{C}$.

Results and Discussion—Silver: The concentration dependence of D_s is shown in Figure 229; the values of b obtained from these data, and the jump frequency ratios calculated therefrom by Howard and Manning⁽²⁹⁹⁾ are shown in Table 82. Values of f from the isotope effect are plotted in Figure 230 as points with error bars; values of f obtained from b via Equation 5 are plotted in Figure 230 as crosses. f calculated by LeClaire⁽²⁹⁷⁾ is shown in this figure as curve "theoretical A"; the curve "theoretical B" was calculated from the jump frequency ratios for 747°C (Table 82) and the

44671

FIG. 229. Diffusion Coefficient of Silver in Silver-Zinc Alloys as a Function of Zinc Concentration for Diffusion at 747°C and 880°C . (The point at $4a/o\text{Zn}$ and 747°C has been ignored when drawing the line; evidently solute-solute interactions are significant here.)

TABLE 82. JUMP FREQUENCY RATIOS NEAR A ZINC IMPURITY IN SILVER

$T, ^\circ\text{C}$	b	w_4/w_0	w_3/w_1	w_2/w_1
747	12.6	1.15	0.27	1.53
880	12.7	1.3	0.39	1.54

ΔH_i 's calculated by LeClaire.⁽²⁹⁹⁾ Since the value of f is relatively insensitive to large ($\sim 10\%$) changes in the jump frequency ratios, the temperature dependence shown in Table 82 was not used. The main difference between the two theoretical curves is in the value of ν_1/ν_0 ; LeClaire⁽²⁹⁷⁾ set this equal to 1.0, but we find that $\nu_1/\nu_0 = 2.9$. Nevertheless, the agreement of both curves with experiment can be considered satisfactory. This leads us to conclude that (1) Equations 2 and 3 for f are good to within the experimental error, i.e. zinc impurity in silver does not affect vacancy jumps more distant than w_4 , and (2) The screened point charge model adequately describes the interaction of zinc with vacancies in silver.

Results and Discussion—Copper: Values of E for the diffusion of zinc in copper are shown in Table 82, and f was obtained from E by using an approximate value of ΔK for copper, 0.75, deduced⁽²⁹³⁾ from the volume of activation for self-diffusion.⁽³⁰¹⁾ The values of f

⁽³⁰⁰⁾ Peterson, N. L., Phys. Rev. **132**, 2471 (1963).

⁽³⁰¹⁾ MacArdle, Patrick, and Tomizuka, C. T., private communication.

for zinc diffusing in copper are also shown in Table 83. They are in good agreement with the value calculated by LeClaire,⁽²⁹⁷⁾ 0.55.

Results and Discussion—CuZn: 50a/oCu–50a/oZn is a concentrated alloy. Therefore Equations 1–3 do not apply to it, and no correlation factor can be gotten from the measured values of E (Table 84). Nevertheless, some qualitative inferences can be drawn. First, since it seems reasonable that ΔK is the same for the ordered and disordered alloys, it is evident that the isotope effect is almost the same for the ordered

44950

FIG. 230. Correlation Coefficient for the Diffusion of Zinc in Silver Plotted vs Reciprocal Absolute Temperature. The points with error bars are data from the isotope effect experiments. The crosses are values calculated from Equation 5. See text for description of the two curves labeled "theoretical."

TABLE 83. ISOTOPE EFFECT FOR THE DIFFUSION OF ZINC IN COPPER

$T, ^\circ\text{C}$	E	f
894.5	0.41 ± 0.003	~ 0.55
946.4	0.41 ± 0.01	~ 0.55

TABLE 84. ISOTOPE EFFECT FOR THE DIFFUSION OF ZINC IN CuZn

Composition	$T, ^\circ\text{C}$	E
50.94a/oCu, balance Zn (disordered)	560.3	0.24 ± 0.006
52.74a/oCu, balance Zn (ordered, $S = 0.7$)	410.6	0.20 ± 0.01

TABLE 85. ISOTOPE EFFECT FOR SELF-DIFFUSION IN ZINC

$T, ^\circ\text{C}$	Direction	$D, \text{cm}^2/\text{sec}$	E	f_{Ax}	f_{Bx}	f_{Bz}	ΔK
411.3	$\parallel C$	1.29×10^{-8}	0.669 ± 0.027	0.803	0.764	0.764	0.87
	$\perp C$	8.48×10^{-9}	0.698 ± 0.012				0.89
382.5	$\parallel C$	6.12×10^{-9}	0.723 ± 0.014	0.809	0.757	0.757	0.96
	$\perp C$	3.80×10^{-9}	0.762 ± 0.015				0.96

and disordered alloys. This means that the details of the diffusion process in the ordered and disordered alloys are quite similar. Specifically, a highly correlated mechanism like the one proposed by Elcock and McCombie,⁽³⁰²⁾ which allows diffusion to take place while maintaining the degree of order, is not dominant in the ordered alloy. Since the degree of long-range order is only 0.7 at the investigated temperature, this is not surprising. The Elcock-McCombie mechanism is a very inefficient means of transport, and is likely to be important only at $S \leq 1$. The results also show that next nearest-neighbor jumps are not important in diffusion in the ordered alloy.

Results and Discussion—Zinc: Preliminary results for isotope effect for self-diffusion in zinc, parallel and perpendicular to the c -axis, are given in Table 85. Appropriate values of f were calculated from the ratios of the D 's.⁽³⁰³⁾ ΔK for the two directions is the same within the experimental error; it appears to decrease as the temperature increases, although this effect needs to be confirmed by more experiments. The data of Table 85 are in excellent agreement with the data of Batra and Huntington.⁽³⁰⁴⁾

⁽³⁰²⁾ Elcock, E. W., and McCombie, C. W., Phys. Rev. **109**, 605 (1958).

⁽³⁰³⁾ Mullen, J. G., Phys. Rev. **124**, 1723 (1961).

⁽³⁰⁴⁾ Batra, A. P., and Huntington, H. B., Bull. Am. Phys. Soc. **11**, 183 (1966).

2. Impurity Diffusion in Aluminum (N. L. PETERSON AND S. J. ROTHMAN)

LeClaire⁽³⁰⁵⁾ has proposed a theory for impurity diffusion in metals based on the picture of an impurity of excess charge Z dissolved in a metal and screened by the conduction electrons. The change in energy of vacancy formation and motion next to an impurity from that in the pure solvent was calculated from the electrostatic interaction of the impurity and vacancy. This interaction was determined from the potential distribution around the impurity as described by the linearized form of the Thomas-Fermi equation.

Although this theory is in good agreement with experiment for diffusion of electropositive impurities in the noble metals (see the preceding report on zinc diffusion in silver, p. 246), it is generally agreed that the Thomas-Fermi equation gives a poor description of the potential about an impurity in most metals.^(306,307) March and co-workers⁽³⁰⁶⁾ and Harrison⁽³⁰⁷⁾ have made more precise calculations and shown that the potential about an impurity is of an oscillatory nature rather than varying exponentially with the distance from the impurity, as stated by the Thomas-Fermi equation. For metals with a low electron density at the Fermi surface, such as the noble metals, the two theories give much the same results out to nearest-neighbor distances, which is all that is important for LeClaire's theory. However, for polyvalent metals like aluminum, the two potentials give different results, even of opposite sign, at the nearest-neighbor distance. It is for this reason that a comprehensive investigation of impurity diffusion in aluminum has been initiated.

Radioactive isotopes of the impurities were evaporated onto freshly etched surfaces of 99.999% pure single crystals of aluminum. After a diffusion anneal in vacuum, the samples were reduced in diameter on a spark cutter and sectioned on a microtome. The sections were weighed and counted and the diffusion coefficient determined in the usual manner. The penetration plots were similar to those shown in last year's Annual Report (ANL-7155, p. 217). Final results have been obtained for the diffusion of Zn⁶⁵ and Ga⁷² and are shown as a function of temperature in Figure 231. These results are described by the equations:

$$D_{\text{Zn} \rightarrow \text{Al}} = 0.256 \pm 0.003$$

$$\exp [-(28,850 \pm 150)/RT] \text{ cm}^2/\text{sec}$$

$$D_{\text{Ga} \rightarrow \text{Al}} = 0.500 \pm 0.005$$

$$\exp [-(29,300 \pm 140)/RT] \text{ cm}^2/\text{sec}.$$

⁽³⁰⁵⁾ LeClaire, A. D., *Phil. Mag.* **7**, 141 (1962).

⁽³⁰⁶⁾ March, N. H., and Murray, A. M., *Proc. Roy. Soc. (London)* **A261**, 119 (1961).

⁽³⁰⁷⁾ Harrison, W. A., *Phys. Rev.* **131**, 2433 (1963).

45981

FIG. 231. Temperature Dependence of Impurity and Self-diffusion in Aluminum.

A reanalysis of the previously reported results of Hilliard et al.⁽³⁰⁸⁾ on zinc diffusing in aluminum, omitting their two highest values of D , is in agreement with our results and may be represented by the equation

$$D_{\text{Zn} \rightarrow \text{Al}} = 0.625 \pm 0.03$$

$$\exp [-(29,800 \pm 310)/RT] \text{ cm}^2 \text{ sec}.$$

The results of Lundy and Murdock⁽³⁰⁹⁾ on the diffusion of Al²⁶ and Mn⁵⁴ in aluminum and the less reliable results of Anand et al.⁽³¹⁰⁾ on the diffusion of Cu⁶⁴ in aluminum are also shown in Figure 231.

Preliminary results have been obtained for the diffusion of Ge⁷¹, Cu⁶⁴ and Au¹⁹⁸ in aluminum single crystals. D_{Ge} appears to be about 10% greater than D_{Ga} with about the same activation energy. Our D_{Cu} is in general agreement with the results of Anand et al.⁽³¹⁰⁾ D_{Au} appears to be a bit smaller than D_{Mn} with about the same activation energy.

Thirteen measurements of the diffusion of Co⁶⁰ in aluminum were made, with only moderate success. All the penetration plots were curved upwards at the surface with the curvature decreasing with increasing temperature. Initially, this was believed to be due to the very small solubility of cobalt in aluminum (maximum

⁽³⁰⁸⁾ Hilliard, J. E., Averbach, B. L., and Cohen, M., *Acta Met.* **7**, 86 (1959).

⁽³⁰⁹⁾ Lundy, T. S., and Murdock, J. F., *J.A.P.* **33**, 1671 (1962).

⁽³¹⁰⁾ Anand, M. S., Murarka, S. P., and Agarwala, R. P., *J.A.P.* **36**, 3860 (1965).

solubility is approximately 90 ppm⁽³¹¹⁾). However, measurements made with two different batches of Co⁶⁰, differing by a factor of 10² in specific activity, gave identical results at the same temperature. Only one of about every ten atoms on the surface of the sample was cobalt for the high specific activity isotope. At present, we think that the cobalt atoms are partially trapped at the sample surface by a thin layer of aluminum oxide. Hence, we have a continuous source of cobalt on the surface, but the source strength varies with time. Since there is no solution for the diffusion equation under these boundary conditions, we do not have reliable values of D_{Co} in aluminum. However, at high temperatures where the curvature is small, $D_{Co} \simeq D_{Ga}$ but the activation energy appears to be appreciably larger than for self-diffusion in aluminum. These results are completely different from those of Hirano et al.⁽³¹¹⁾ They deposited very low specific activity cobalt onto polycrystalline aluminum, so that the cobalt concentration on the sample surface after diffusion exceeded the solubility limit by several orders of magnitude. They interpreted their results as being representative of diffusion only along grain boundaries and dislocations.

Impurities both to the left of aluminum (i.e. Zn) and to the right of aluminum (i.e. Ge) in the periodic table diffuse faster than aluminum self-diffusion. This is inconsistent with any simple theory of impurity diffusion based on the electrostatic interaction between

⁽³¹¹⁾ Hirano, K., Agarwala, R. P., and Cohen, M., *Acta Met.* **10**, 857 (1962).

impurities and vacancies. This may be due to either (1) that the impurities do not pick up or give off electrons to make their electron core similar to aluminum (i.e. the values of Z are not what we expect) or (2) the position of the minimum of the oscillating potential shifts slightly from one impurity to another. In either case the model of the saddle point used in the LeClaire theory does not seem adequate to describe impurity diffusion in aluminum.

All the impurities diffuse with much the same activation energy (~ 29 kcal/mole) which is a bit smaller than the activation energy for self-diffusion (~ 32 kcal/mole). Hence it appears that all the impurities have a slight attraction for vacancies (≤ 3 kcal/mole). These small impurity-vacancy binding energies are consistent with the high-temperature equilibrium results of Beaman, Balluffi and Simmons⁽³¹²⁾ on Al-Ag and Al-Mg alloys, but are inconsistent with some of the large binding energies observed in quenching studies in aluminum alloys.⁽³¹³⁾ This discrepancy may well be due to clustering or precipitation during the quench, such that the true state of the alloy at high temperature is not retained by quenching. Further studies of impurity diffusion and a more careful analysis of the quenching experiments are needed before a clear picture of impurity-vacancy binding in aluminum can be obtained.

⁽³¹²⁾ Beaman, D. R., Balluffi, R. W., and Simmons, R. O., *Phys. Rev.* **134**, A532 (1964); *ibid.* **137**, A917 (1965).

⁽³¹³⁾ These are reviewed by Doyama, M., *Phys. Rev.* **148**, 681 (1966).

3. Diffusion in Grain Boundaries (N. L. PETERSON)

The theoretical basis for this experiment was stated in last year's Annual Report (ANL-7155). Progress on these experiments has been limited to growing the

crystals and obtaining the necessary counting equipment for the isotope effect measurements on the simultaneous diffusion of Ag¹⁰⁵ and Ag¹¹¹.

F. TRANSITION METALS AND ALLOYS

1. Magnetic Properties

a. MAGNETIC MOMENTS IN IRON AND NICKEL ALLOYS (A. T. ALDRED AND D. I. BARDOS)

Publications

A. T. Aldred, *Magnetization of Iron-Beryllium Alloys*, J. Appl. Phys. **37**, 671 (1966).

A. T. Aldred, *Magnetization of Iron-Gallium and Iron-Arsenic Alloys*, J. Appl. Phys. **37**, 1344 (1966).

D. I. Bardos, A. T. Aldred and P. A. Beck, *The Effect of Aluminum on the Saturation Moments of Fe-Ni Alloys*, 12th Annual Conference on Magnetism and Magnetic Materials, 1966 [Abstract].

The study of magnetic moments in iron and nickel alloys has continued in two areas, namely: (a) binary bcc iron-rich solid solutions, and (b) the fcc nickel-rich and bcc iron-rich solid solutions in the Fe-Ni-Al ternary system.

The apparatus for measuring saturation magnetizations was modified during 1966, although the experimental techniques employed remained the same. A new Varian 15 in. magnet with pole pieces having a constant field gradient was installed, together with a new cryostat that enabled the sample to be positioned accurately at any temperature. The experimental difficulties mentioned in ANL-7000 have now been overcome.

The measurements on binary iron-rich alloys are almost complete. The additional data that have been obtained are given in Table 86, which lists for the various alloys, $\sigma_{\infty,0}$ (emu/g) the saturation magnetization at absolute zero, A ($^{\circ}\text{K}^{-3/2} \times 10^6$) the coefficient of the $T^{3/2}$ extrapolation, $\bar{p}_B$ the mean atomic moment, and $(p_R)\text{Fe}$ the moment per iron atom. The data for pure iron are taken from the literature.^(314,315)

If the mean atomic moment in any alloy system is plotted against solute concentration, N_{sol} , an initial linear decrease of the mean moment is obtained. The data have therefore been submitted to a least-squares analysis to obtain equations of the form

$$\bar{p}_B = A - BN_{\text{sol}} \quad (1)$$

The coefficients A and B for the various solutes are given in Table 86 together with the probable errors for 95% confidence limits. The value for pure iron was used in each of the analyses except for the cases of titanium or gold as the solute, where it was evident from graphical observation that the data did not ex-

trapolate back to the origin at the value for pure iron. This can be seen from the values of A for titanium and gold in Table 87. For comparison the results for the iron-gold alloys were also calculated with the value for pure iron included, and this equation is also listed (with 4 data points). It can be seen that the least-squares fit is significantly worse than in the first case.

The first point of interest is the one noted above, namely that, particularly for the case of iron-titanium alloys, the data do not extrapolate back to the value for pure iron. The only other iron system where this has been observed is iron-vanadium⁽³¹⁶⁾ where the intercept is 2.232. In both of these systems, there must be a change in slope of the magnetic moment vs concentration curve at a solute concentration less than 2 a/o.

Examination of the values for the slope B shows that only in the cases of molybdenum, tungsten or copper in iron is B even approximately equal to the intercept A , corresponding to the dilution model in which the solute atoms carry no moment themselves but simply dilute a constant iron moment. Molybdenum and tungsten both belong to Group VIB; the first long period element from this group, chromium, when alloyed with iron gives a somewhat higher slope of 2.36.⁽³¹⁶⁾ However, neutron diffraction results⁽³¹⁷⁾ indicate that iron does indeed retain its moment of 2.2 μ_B but there is an antiparallel moment on the chromium atoms.

The elements from Group VIIB, technetium and rhenium, when alloyed with iron give similar values of B but they correspond to a slope less than dilution, implying either a small increase in the iron moment to a maximum of 2.3 μ_B or a parallel moment on the solute atoms. The first long period member of Group VIIB, manganese, again gives a higher value of B ⁽³¹⁸⁾ although the data are suspect because of the long annealing times required to produce homogeneous equilibrium alloys in this system.⁽³¹⁹⁾ If this higher value of B is real, it could again be explained by an antiparallel moment on the solute (manganese) atoms, but there are no neutron diffraction data to support this conclusion.

⁽³¹⁶⁾ Nevitt, M. V., and Aldred, A. T., J. App. Phys. **34**, 463 (1963).

⁽³¹⁷⁾ Shull, C. G., in *Theory of Alloy Phases* A.S.M., Cleveland, Ohio (1956).

⁽³¹⁸⁾ Sadron, C., Ann. Phys. **IV**, 371 (1932).

⁽³¹⁹⁾ Troiano, A. R. and McGuire, F. T., Trans. A. S. M. **31**, 340 (1943).

⁽³¹⁴⁾ Weiss, P. and Forrer, R., Ann. Phys. **12**, 279 (1929).

⁽³¹⁵⁾ Danan, H., Comptes Rendus **246**, 73 (1958).

TABLE 86. MAGNETIZATION AND HEAT TREATMENT DATA FOR BINARY BCC IRON ALLOYS

Solute	a/o Solute	Heat Treatment		$\sigma_{\infty,0}$ (emu/g)	$A \times 10^6$ (°K ^{-3/2})	$\bar{\mu}_B$ (μB/at.)	$(\bar{\mu}_B)_{Fe}$ (μB/at. Fe)
		Temp (°C)	Time (hr)				
Pure Fe	0			221.75	3.74	2.218	2.218
Ti	2.02	1251	72	217.31	3.91	2.167	2.212
	4.00	—	—	211.09	3.63	2.099	2.186
	5.97	—	—	205.05	3.87	2.033	2.162
Mo	2.13	1440	1/2	214.46	3.98	2.177	2.224
	3.05	1400	6 1/2	211.50	4.35	2.161	2.229
	5.10	1440	1/2	204.47	4.57	2.119	2.233
	6.14	1400	6 1/2	200.38	4.76	2.092	2.229
	10.33	1440	1/2	186.45	5.82	2.002	2.233
	12.20	1400	6 1/2	179.48	6.18	1.952	2.223
W	2.00	1465	5 1/2	208.29	3.99	2.178	2.222
	2.92	1503	6	202.41	4.16	2.159	2.224
	4.98	1465	5 1/2	190.24	4.30	2.119	2.230
	6.00	1503	6	184.20	4.38	2.095	2.229
Tc	8.03	1513	6	173.55	4.81	2.054	2.233
	10.01	1503	6	162.68	4.74	2.000	2.222
	2.00	900	336	215.82	4.82	2.191	2.236
	5.00	—	—	206.86	6.29	2.148	2.261
Re	8.00	—	—	198.34	7.26	2.106	2.289
	11.00	—	168	188.02	8.62	2.040	2.292
	2.00	800	336	209.12	3.95	2.188	2.233
	3.00	811	168	202.96	4.07	2.171	2.238
	4.84	—	—	192.73	4.59	2.145	2.254
	5.86	800	336	187.15	4.87	2.127	2.259
	8.00	—	—	175.98	5.62	2.088	2.271
	10.05	811	168	167.02	6.39	2.062	2.292
Cu	12.04	—	—	158.69	7.09	2.033	2.311
	14.96	800	168	143.25	8.21	1.932	2.272
	1.32	835	336	218.85	4.44	2.192	2.221
Au	3.00	—	—	215.16	4.64	2.160	2.227
	1.75	1170	72	211.50	5.00	2.208	2.247
	4.03	—	—	198.45	5.96	2.187	2.279
	6.14	—	—	187.60	6.61	2.167	2.309

TABLE 87. COEFFICIENTS OF THE EQUATION $\bar{\mu}_B = A - BN_{sol}$ FOR VARIOUS SOLUTES IN IRON

Solute	A	B	No. of Points	Highest Solute Conc. (a/o)
Ti	2.235 ± 0.002	3.392 ± 0.049	3	5.97
Mo	2.222 ± 0.005	2.105 ± 0.090	6	10.33
W	2.219 ± 0.002	2.044 ± 0.038	6	8.03
Tc	2.218 ± 0.001	1.405 ± 0.019	4	8.00
Re	2.218 ± 0.003	1.557 ± 0.049	8	12.04
Cu	2.218 ± 0.001	1.932 ± 0.037	3	3.00
Au	2.224 ± 0.001	0.934 ± 0.015	3	6.14
Au	2.220 ± 0.004	0.844 ± 0.114	4	6.14

The magnetic moment data for gold dissolved in iron yield a slope that is considerably less than would be expected from the dilution model. It would seem appropriate to rationalize this result in terms of an increase in the iron moment rather than in terms of a parallel gold moment. Measurements on fcc gold-rich

solid solution alloys⁽³²⁰⁾ show that although alloys containing more than 11 a/o iron are ferromagnetic, there is no evidence for polarization of the matrix atoms as occurs when iron is dissolved in palladium or platinum.⁽³²⁰⁾

Overall consideration of the effect of different transition metal solutes on the slope of the magnetic moment versus concentration curves shows that solutes from the same group have approximately the same value of B . In addition, as the group number of the solute increases, the negative values of B decreases, and in the case of the solutes to the right of iron in the periodic table, B actually becomes positive.⁽³²¹⁾ Analysis of the data in terms of group number of the solute and electron concentration is continuing.

It was pointed out in the 1965 Annual Report (ANL-7155) that the addition of a nontransition metal solute such as aluminum to iron does not affect the moment on iron (iron-type behavior), while the addition of aluminum to nickel decreases the nickel moment by an amount proportional to the valence of aluminum (nickel-type behavior). In order to determine if these different characteristics of iron and nickel are inherent properties of the atomic species or simply related to the different environments of the bcc and fcc structures, saturation magnetization measurements have been made on the fcc nickel-rich and bcc iron-rich solid solutions in the iron-nickel-aluminum system. Six series of alloys were made up, three in the fcc and three in the bcc regions, in which the iron-to-nickel ratio was kept constant as the aluminum concentration was increased.

The results for the fcc alloys were shown graphically in Figure 210 of ANL-7155, which includes the data of Crangle and Martin⁽³²²⁾ for the nickel-aluminum binary system. A least squares analysis of the four series of alloys yield the following equations:

Ni-Al

$$\bar{\mu}_B = 0.606 \pm 0.0002 - 2.78 \pm 0.03N_{Al}$$

Fe:Ni = 1:4

$$\bar{\mu}_B = 1.059 \pm 0.001 - 2.64 \pm 0.04N_{Al}$$

Fe:Ni = 2:3

$$\bar{\mu}_B = 1.488 \pm 0.001 - 3.13 \pm 0.02N_{Al}$$

Fe:Ni = 3:2

$$\bar{\mu}_B = 1.818 \pm 0.0004 - 3.87 \pm 0.02N_{Al} - 20.14 \pm 0.02N_{Al}^2$$

⁽³²⁰⁾ Crangle, J. and Scott, W. R., J. Appl. Phys **36**, 921 (1965).

⁽³²¹⁾ Fallot, M., Ann. Phys. **10**, 291 (1938).

⁽³²²⁾ Crangle, J. and Martin, M.T.C., Phil. Mag. **4**, 1006 (1959).

It is evident that as the iron-to-nickel ratio is increased, the iron-type behavior is not being approached, since dilution of a constant moment would require the value of the slope to equal the value of the intercept in the above relations. However, the data can be satisfactorily explained if the following assumptions are made: (1) the rate of decrease of the average nickel moment with increasing aluminum concentration is the same as in nickel-aluminum binary alloys, (2) the average iron moment is changed only as the number of nickel nearest neighbors is reduced by the addition of a aluminum.

The dependence of the iron moment on nickel concentration in binary iron-nickel alloys has been investigated by means of neutron magnetic scattering experiments.^(317,323) The data for disordered alloys from these investigations are plotted in Figure 232 along with the probable error limits. The nickel moment remains approximately constant over a relatively large concentration range, while the average iron moment increases with increasing nickel concentration. This increase is apparently associated with the number of nickel atoms that are nearest neighbors to each iron atom.

If aluminum is added to a binary nickel-iron alloy, the number of nickel atoms that are nearest neighbors to an iron atom is reduced, even though the ratio of iron to nickel remains constant and, therefore, there is a reduction in the iron moment, although aluminum is acting as a diluent. For example, if aluminum is added in amounts of 2, 5, and 10 at.% to a 60a/oNi-40a/oFe alloy, the nickel concentration decreases to 58.8, 57, and 54 a/o respectively, and there is a corresponding decrease in the iron moment as indicated by the symbol $\times$ in Figure 232.

The three series of bcc alloys that are being investigated have iron-to-nickel ratios of 92:8, 84:16 and 75:25. Alloys containing 10 a/o or more of aluminum were annealed at 700°C for 7 days to obtain the equilibrium bcc structure, which was retained upon water quenching to room temperature. When the aluminum concentration was less than 10 a/o aluminum, the bcc structure was obtained by quenching the alloys from the fcc region at 1050°C into liquid nitrogen in order to induce a martensitic transformation. The completion of these transformations was confirmed by metallographic examination.

The saturation magnetizations and the average atomic magnetic moments obtained to date are listed in Table 88. While the data are not complete, it is apparent that there is a large decrease in the average atomic moment with increasing aluminum concentration. This decrease suggests that the iron moment in

44707

FIG. 232. Atomic Moments (in Bohr Magnetons) Associated with Fe and Ni Atoms in fcc Fe-Ni alloys vs Composition. Filled symbols are from refs. 317 and 323, $\times$'s are explained in the text.

TABLE 88. MAGNETIZATION DATA FOR BCC Fe-Ni-AL ALLOYS

Alloy Composition, at. %			$\sigma_{\infty,0}(\text{emu/g})$	$\bar{\mu}_B(\mu_B/\text{at.})$
Fe	Ni	Al		
92.0 ^(a)	8	0	226.74	2.276
87.4	7.6	5	211.84	2.071
82.8	7.2	10	196.50	1.870
78.2	6.8	15	188.45	1.744
84.0 ^(a)	16	0	224.36	2.261
82.3 ^(a)	15.7	2	220.00	2.194
79.8 ^(a)	15.2	5	210.57	2.070
75.6	14.4	10	193.98	1.853
71.4	14.6	15	172.50	1.603
73.5 ^(a)	24.5	2	205.28	2.057
71.2 ^(a)	23.8	5	195.83	1.931
67.5 ^(a)	22.5	10	179.60	1.723
63.8 ^(a)	21.2	15	164.49	1.535

^(a) Alloys obtained by a martensitic transformation.

these alloys decreases with aluminum concentration in contrast to binary iron-aluminum alloys with similar aluminum contents.

b. MAGNETIC SUSCEPTIBILITIES OF Pt- AND Pd-BASE ALLOYS (D. J. LAM AND K. M. MYLES)

Publications

D. J. Lam and K. M. Myles, *The Magnetic Susceptibilities of Pd-Cd, Pd-Sb and Pt-Cu Binary Alloys*, J. Phys. Soc. Japan **21**, 1503-1507 (1966).

A full account of this alloy system was given in the 1965 Annual Progress Report (ANL-7155). The final results are summarized in the above publication.

⁽³²³⁾ Collins, M. F., Jones, R. V. and Lowde, R. D., J. Phys. Soc. Japan **17**, Suppl. BIII, 19 (1962).

2. Structures and Correlative Scheme of Occurrence of Intermediate Phases

(A. E. DWIGHT)

Publications

A. E. Dwight, J. W. Downey, and R. A. Conner, Jr., *Laves Phases of the Scandium Group Elements with Ruthenium, Rhodium, Osmium, Iridium and Platinum*, Trans. Met. Soc. AIME **236**, 1509 (1966).

A. E. Dwight, *ZrX₂ Compounds*, Abstract Bulletin of the Institute of Metals Division, AIME 1, No. 2, 52 (1966).

A number of new intermetallic compounds with the KHg₂-type structure are listed in Table 89. Both KHg₂ and CeCu₂ are cited in the literature as the prototype compounds. KHg₂ was reported⁽³²⁴⁾ in 1955 and CeCu₂⁽³²⁵⁾ in 1961, and it was not recognized that

TABLE 89. INTERMETALLIC COMPOUNDS WITH THE KHg₂-TYPE STRUCTURE

Compound	<i>a</i> ₀	<i>b</i> ₀	<i>c</i> ₀	Vol./ <i>M</i> , (Å) ³
YNiGa	4.30	6.90	7.32	54.3
SMNiGa	4.35	6.97	7.41	56.1
GdNiGa	4.32	6.93	7.36	55.2
TbNiGa	4.30	6.88	7.35	54.3
DyNiGa	4.29	6.87	7.34	54.0
HoNiGa	4.279	6.829	7.329	53.5
ErNiGa	4.262	6.789	7.315	52.9
TmNiGa	4.24	6.75	7.31	52.3
YbNiGa	4.25	6.76	7.33	52.7
LuNiGa	4.21	6.67	7.29	51.3

TABLE 90. INTERATOMIC DISTANCES, COORDINATION NUMBERS AND DENSITIES OF HoNiGa

Space group: Imma, No. 74

Ho in 4e: 0, ½, *z*, with *z* assumed to be 0.538.⁽³²⁵⁾

Ni and Ga in 8h: 0, *y*, *z*, with *y* assumed to be 0.051 and *z* 0.165.⁽³²⁵⁾

Interatomic Distances, Å			
Ho-2Ho	3.46	(Ni,Ga)-2Ho	2.94
Ho-2Ho	3.78	(Ni,Ga)-1Ho	2.99
Ho-4(Ni,Ga)	2.94	(Ni,Ga)-1Ho	3.05
Ho-2(Ni,Ga)	2.99	(Ni,Ga)-2Ho	3.11
Ho-2(Ni,Ga)	3.05	(Ni,Ga)-2(Ni,Ga)	2.48
Ho-4(Ni,Ga)	3.11	(Ni,Ga)-1(Ni,Ga)	2.51
		(Ni,Ga)-1(Ni,Ga)	2.72
Density from unit cell: 9.10 g/cc			
Density by immersion: 9.13 g/cc			

⁽³²⁴⁾ Duwell, E. J. and Baeniziger, N. C., *The Crystal Structures of KHg and KHg₂*, Acta Cryst. **8**, 705 (1955).

⁽³²⁵⁾ Larson, A. C. and Cromer, D. T., *The Crystal Structure of CeCu₂*, Acta Cryst. **14**, 73 (1961).

45984

FIG. 233. The Structure of the Orthorhombic HoNiGa Compound, KHg₂-type.

the two are isostructural. KHg₂, by virtue of earlier discovery, is designated as the prototype in this report.

The KHg₂-type compound HoNiGa was selected for the determination of density, interatomic distances and coordination numbers. These are given in Table 90. The crystal structure, shown in Figure 233, is orthorhombic, although as noted for CeCu₂,⁽³²⁶⁾ the structure may be considered as an orthorhombic distortion of the hexagonal AlB₂ type. A dominant feature of the structure is the zig-zag chains of Ho atoms, which run parallel to the *b*₀ axis. Figure 234, which is a plot of *a*₀, *b*₀, *c*₀ and *V*/*M* against atomic numbers of the lanthanide series, shows that the *b*₀ contracts more rapidly than *a*₀ or *c*₀, with increasing atomic number. Since in the rare-earth series, increasing atomic number means decreasing atomic volume (with two exceptions), the contraction in *b*₀ in Figure 234 is attributed to the close contact between the rare-earth atoms parallel to this dimension of the unit cell.

An interesting observation concerning HoNiGa is that it is isostructural with HoCu₂⁽³²⁶⁾ and HoZn₂.⁽³²⁷⁾ This indicates that Cu in HoCu₂ (or Zn in HoZn₂) may be replaced with a mixture of two elements, one (Ni) lying to the left of Cu in the periodic table, and the other (Ga) lying to the right. This is a rare example wherein Cu may be synthesized by two nearby elements.

⁽³²⁶⁾ Storm, A. R. and Benson, K. E., *Lanthanide-copper Compounds having the CeCu₂ and AlB₂ Structures*, Acta Cryst. **16**, 701 (1963).

⁽³²⁷⁾ Michel, D. J. and Ryba, E., *The Crystal Structure of HoZn₂*, Acta Cryst. **21**, 818 (1966).

45986

FIG. 234. The Unit Cell Constants of KHg_2 -type Compounds of R.E.-NiGa Composition, in which R.E. Includes Y and the Lanthanides Sm, Gd through Lu.

Yttrium may also be alloyed with Ni and Ga to form YNiGa with the KHg_2 -type structure. Since Y has a much lower atomic number than the lanthanide elements, Y must occupy a special position on plots of unit-cell data vs atomic number as shown in Figures 234, 235 and 236. The basis on which Y data is located on the figures is to place the atomic volume/mole, (V/M), for the Y compound such that it lies on the V/M curve for the lanthanide series. It has been noted from the study of this and other series of lanthanide compounds, that Y compounds have an atomic volume slightly larger than that of their Tb counterpart, and thus Y always appears between Tb and Dy on a plot of this type. The individual cell constants for YNiGa are placed in accordance with the location of the V/M value.

YbNiGa has values of a_0 , b_0 , c_0 and V/M that lie above the curves for the other compounds in Figure 234. This is consistent with the tendency of Yb to exhibit a valence less than three, and a larger atomic volume in certain of its compounds.

A large family of Fe_2P -type compounds have been identified and are listed in Table 91. A structure for the prototype Fe_2P was reported incorrectly by Hendricks and Kosting⁽³²⁸⁾ but a later investigation by Rundqvist and Jellinek⁽³²⁹⁾ gave the correct structure. The most recent tabulation⁽³³⁰⁾ of Fe_2P -type com-

45987

FIG. 235. The Unit Cell Constants of Fe_2P -type Compounds of R.E.-NiAl Composition, in which R.E. Includes Y, Ce, Nd, Sm, Gd through Tm, and Lu.

45982

FIG. 236. The Unit Cell Constants of Fe_2P -type Compounds of R.E.-CuAl Composition, in which R.E. Includes Y, Ce, Pr, Nd, Sm, Gd through Lu.

pounds does not include any compounds with a rare earth component. In an independent investigation, Lam, et al.⁽³³¹⁾ reported UFeAl , UCoAl and UIrAl as

(331) Lam, D. J., Darby, J. B., Jr., Downey, J. W., and Norton, L. J., *Equiatomic Ternary Compounds of U and Al with Group VIII Transition Elements*, accepted for publication, J. Nucl. Materials.

(328) Hendricks, S. B. and Kosting, P. R., *The Crystal Structure of Fe_2P , Fe_2N , Fe_2B , and Fe_2S* , Z. Krist. **74**, 511 (1930).

(329) Rundqvist, S., and Jellinek, F., *The Structures of $\text{Ni}_6\text{Si}_2\text{B}$, Fe_2P and Some Related Phases*, Acta Chem. Scand. **14**, 425 (1959).

(330) Schubert, K., in the book, *Kristallstrukturen zweikomponentiger Phasen*, 325 Springer-Verlag (1964).

TABLE 91. INTERMETALLIC COMPOUNDS WITH THE Fe_2P -TYPE STRUCTURE

Compound	a_0	c_0	c/a	$\text{Vol.}/M, (\text{\AA})^3$
CeNiGa	6.95	3.98	0.57	55.4
YNiAl	7.04	3.83	0.54	54.8
CeNiAl	6.97	4.02	0.58	56.4
NdNiAl	7.02	4.06	0.58	57.8
SmNiAl	6.99	4.00	0.57	56.5
GdNiAl	7.03	3.92	0.56	55.9
TbNiAl	7.003	3.877	0.554	54.9
DyNiAl	7.00	3.84	0.55	54.3
HoNiAl	6.989	3.820	0.547	53.9
ErNiAl	6.974	3.798	0.545	53.3
TmNiAl	6.97	3.77	0.54	53.0
LuNiAl	6.92	3.75	0.54	51.9
YCuAl	7.04	4.03	0.57	57.6
CeCuAl	7.17	4.20	0.59	62.3
PrCuAl	7.173	4.154	0.579	61.7
NdCuAl	7.169	4.122	0.575	61.2
SmCuAl	7.121	4.083	0.573	59.8
GdCuAl	7.078	4.065	0.574	58.8
TbCuAl	7.041	4.044	0.574	57.9
DyCuAl	7.023	4.025	0.573	57.3
HoCuAl	6.997	4.015	0.574	56.7
ErCuAl	6.974	4.002	0.574	56.2
TmCuAl	6.945	3.996	0.575	55.6
YbCuAl	6.92	3.98	0.57	55.1
LuCuAl	6.905	3.994	0.578	55.0
ThCoAl	7.047	4.036	0.573	57.9
ThNiAl	7.080	4.055	0.573	58.7
ThRhAl	7.183	4.120	0.574	61.4
ThIrAl	7.176	4.142	0.577	61.6
ThPtAl	7.271	4.154	0.571	63.4
ThCoGa	7.06	3.98	0.56	57.1
ThNiGa	7.05	4.02	0.57	57.8
ThRhGa	7.214	4.044	0.561	60.8
ThIrGa	7.22	4.07	0.56	61.3
ThPtGa	7.297	4.094	0.561	62.9
UNiAl	6.733	4.035	0.599	52.8
URhAl	6.965	4.019	0.577	56.3
UPtAl	7.012	4.127	0.589	58.6
UFeGa	6.72	3.90	0.58	50.8
UCoGa	6.693	3.933	0.588	50.9
UNiGa	6.733	4.022	0.597	52.6
URhGa	7.006	3.945	0.563	55.9
UIrGa	7.033	3.944	0.561	56.3
UPtGa	7.063	4.064	0.575	58.5
ZrNiAl	6.916	6.941	1.004	47.9
ZrPtAl	7.108	7.210	1.014	52.6
ZrNiGa	6.893	6.872	0.997	47.1
ZrPtGa	7.143	7.069	0.990	52.1
HfNiAl	6.885	6.838	0.993	46.8
HfPtAl	7.094	7.114	1.003	51.7
HfNiGa	6.866	6.758	0.984	46.0
HfPtGa	7.123	6.995	0.982	51.2

examples of the Fe_2P structure. Steeb and Petzow⁽³³²⁾ reported the existence of UCoAl , UNiAl and UIrAl with the same structure.

⁽³³²⁾ Steeb, S., and Petzow, G., *On the Ternary Phases UCoAl, UIrAl and UNiAl of the C22 (Fe_2P)-type*, accepted for publication, Trans. Met. Soc. AIME.

Table 91 also includes the data for four Zr and four Hf compounds closely related to the Fe_2P -type structure. The X-ray diffraction patterns of these eight compounds contain all the lines of the Fe_2P -type structure and in addition some weak lines that can be indexed only by doubling the c_0 of the unit cell. The structure is believed to be a variant of the Fe_2P -type, but the exact type is not yet known.

The crystal structure of HoNiAl , a Fe_2P -type compound, is shown in Figure 237. It is a layer structure with ABAB stacking. A distinguishing feature is that all Ho atoms are in the *A* layer, all Al atoms are in the *B* layer, but the Ni atoms are distributed in both *A* and *B* layers. Table 92 gives interatomic distances and coordination numbers for HoNiAl . The interatomic distances are tentative since they are dependent upon atomic positional parameters published for the compound Fe_2P ,⁽³²⁹⁾ and it is recognized that values for a phosphide are likely to differ from those for a metallic compound. The interatomic distances reveal

45983

FIG. 237. The Structure of the Hexagonal HoNiAl Compound, Fe_2P -type.TABLE 92. INTERATOMIC DISTANCES AND COORDINATION NUMBERS OF HoNiAl Space group: $\text{P}\bar{6}2\text{m}$, No. 189Ho in 3g: $x, 0, \frac{1}{2}$, with x assumed to be 0.594.⁽³²⁹⁾Ni in 1b: $0, 0, \frac{1}{2}$ Ni in 2c: $\frac{1}{2}, \frac{2}{3}, 0$ Al in 3f: $x, 0, 0$ with x assumed to be 0.256.⁽³²⁹⁾Interatomic Distances, $\text{\AA}$

Ho-2Ho	3.82	Ni-3Al	2.64
Ho-4Ho	3.68	Ni-6Ho	2.85
Ho-1Ni	2.84	Al-2Ni	2.62
Ho-4Ni	2.85	Al-2Ni	2.64
Ho-2Al	3.04	Al-4Ho	3.13
Ho-4Al	3.13	Al-2Al	3.10
Ni-6Al	2.62	Al-2Ho	3.04
Ni-3Ho	2.84		

the dominant reason for the stability of the Fe_2P -type structure in ternary compounds. The distance from a Ho atom to 5 Ni atoms is substantially less than the distance from a Ho atom to 6 Al atoms. This difference in interatomic distances favors the choice of two atomic species with substantial atomic size differences which can be accommodated in the shell of eleven atoms surrounding the Ho atom.

The unit-cell constants and molar volumes for the rare earth-NiAl compounds are shown in Figure 235. Substitution of a small rare earth for a large one (as Lu for Nd) causes almost no change in a_0 but a steady decrease in c_0 , c/a , and V/M values. CeNiAl is the exception, with values lower than normal. In contrast to this trend, the data for the rare earth-CuAl compounds shown in Figure 236, exhibit a nearly constant a_0 value for Ce-, Pr-, and NdCuAl, while a steady decrease is observed in a_0 for the remaining rare-earth compounds. The curve for c_0 also decreases and results in a nearly constant c/a ratio. It is probable that the smaller size of Ni compared with Cu is responsible for the difference in trends between the R.E.-NiAl and R.E.-CuAl series.

A comparison of Figures 235 and 236 shows a marked difference between the atomic size of Ce in CeNiAl and in CeCuAl. The abnormally low volume of the compound CeNiAl indicates that the Ce atom has an effectively higher valence than the valence of three that it usually assigned to the rare earth elements. However, the V/M value in the compound CeCuAl lies on the volume curve, and apparently Ce has the normal valence of three. This observed variation in the volume of Ce compounds is consistent with observations made by other writers. Raynor⁽³³³⁾ has noted that the apparent volume of cerium, both elemental and in compounds, is sensitive to compressive strain energy and that contraction may be attributed

(333) Raynor, G. V. *Electronic States of Rare-Earth Metals in Alloys*, Proceedings of the Fifth Rare-Earth Research Conference, Book 5, p. 1 (1965).

3. Thermodynamic Properties

a. LOW-TEMPERATURE SPECIFIC HEATS (L. L. ISAACS)

Publications (Work done at Mellon Institute, Pittsburgh, Pa.)

L. L. Isaacs and T. B. Massalski, *Low-Temperature Specific Heats Alloys Based on the Noble Metals, Cu, Ag, Au: ζ -Phase Ag-Sn Alloys*, Phys. Rev. **141**, 634 (1966).

45985

FIG. 238. Areas of Stability for HoX_2 Intermetallic Compounds.

to ionization of the 4f electrons. He also observed that Ce in CeSn_3 behaves with a valence higher than three, but in CeIn_3 it behaves as a normal trivalent element. Raynor noted further that in the R.E.-Pd³ series Eu and Yb act as normal trivalent metals but Ce has a higher valence.

The construction of plots showing the areas of compositional stability of intermetallic compounds has continued. Figure 238 shows an area-of-stability plot for HoX_2 compounds. The HoNiGa compound, discussed earlier, is an example of a ternary compound that was predicted to occur by straddling an area of stability defined by the binary compounds HoCu_2 and HoZn_2 . In contrast, the occurrence of the Fe_2P -type compound HoNiAl could not be predicted since there is no area of binary stability for this structure. However, now that an area of ternary stability has been found in the HoX_2 and fourteen other area-of-stability plots, some predictions can be made about $\text{Fe}_2\text{-P}$ type compounds not yet discovered. In particular, the transuranium elements may be expected to form Fe_2P -type compounds also, of which AmNiAl may be predicted as one example.

G. A. Sargent, L. L. Isaacs and T. B. Massalski
Low-Temperature Specific Heats of α -Phase Copper-Silver Alloys, Phys. Rev. **143**, 420 (1966).

The experimental techniques that yield the topology of the Fermi surface of metals are the most direct means available for investigating the electronic structure of metals. The application of these techniques to alloys is severely limited by the requirement that the

45938

FIG. 239. A Schematic Diagram of the Low-temperature Calorimeter.

conduction electrons have a relatively long mean-free path; a condition not generally fulfilled in concentrated alloys. Therefore, it is necessary to carry out bulk property measurements, such as the electronic specific heat, the magnetic susceptibility, and nuclear magnetic resonance, in order to calculate the density of states for the alloys and then attempt to infer information concerning the Fermi surface.

A program has been initiated during 1966 to design and construct a low-temperature He^3 calorimeter suitable for determining the low-temperature specific heats of metals and alloys. The calorimeter has been designed to attain temperatures as low as 0.3°K ; this will improve the accuracy of data obtained by extrapolating to absolute zero. The facility has been designed to accommodate a superconducting magnet that will provide the magnetic field necessary to suppress the superconducting state that may exist in certain alloys at low temperatures.

A schematic diagram of the calorimeter is shown in Figure 239. A vacuum-tight sample chamber is in thermal contact with the He^3 -bath. The specimen is placed in thermal contact with the bottom of the He^3 evaporator by means of a mechanical heat switch (not shown). The He^3 gas at room temperature is com-

pressed by the exhaust stage of a suitable mechanical pump. The He^3 gas is purified by passing it through an oil trap at room temperature, and additional traps maintained at 77°K and 4°K . Partial liquification is obtained by passage of the gas through a condenser coil immersed in a heat exchanger where the temperature is kept at approximately 1.2°K by pumping on liquid He^4 . Complete liquification is obtained by throttling the fluid through a porous plug in the delivery tube between the heat exchanger and the evaporator. The temperature of the evaporator and, hence, the sample chamber is further lowered by pumping on the evaporator with a diffusion pump. This refrigeration cycle is operated as a closed loop. The design estimate for the refrigeration capability is 0.1 milliwatt at 0.33°K , 1 milliwatt at 0.4°K and 28 milliwatts at 1.0°K . The sample chamber, evaporator and heat exchanger are enclosed in a common vacuum shield, which is surrounded by a standard helium-nitrogen dewar combination. The sample chamber and vacuum shield are constructed in the form of concentric cylinders with an adequate volume between the vacuum shield and the inner wall of the He^4 dewar to install the superconducting solenoid magnet.

The specific-heat data will be collected by the discontinuous heating technique. The specimen is cooled to the lowest temperature obtainable by the apparatus. Then the specimen is isolated from the sample chamber by means of the mechanical heat switch. The sample temperature as a function of time is measured via a sensor attached to the specimen to determine the effects of stray energy inputs to the sample due to imperfect isolation. After the specimen temperature has been monitored for a sufficient length of time, the specimen is heated by passing a current through a resistance coil wrapped around the specimen. At the end of the heating period the specimen temperature is again monitored until steady state conditions are obtained. The sequence is repeated until the temperature range of interest is completely scanned.

The temperature sensor is a germanium resistor that is calibrated as a thermometer against the vapor pressures of He^3 and He^4 . A vapor pressure bulb is built into the sample chamber to facilitate this calibration procedure. The resistance is measured potentiometrically by means of a high-precision digital voltmeter. The voltmeter is also used to determine the energy inputs during the heating cycle.

After the installation and calibration of the apparatus have been completed, the initial experiments will be performed to determine the low-temperature specific heats of the hexagonal transition metals and their alloys of the second long period of the periodic table. The density of states will be calculated

to provide a complete series for this period as has been done for the first long period. The specific alloy systems to be investigated initially will include the complete series of solid solutions in the Tc-Ru system and the hexagonal terminal solid solutions in the Tc-Rh and Ru-Rh systems.

b. THERMODYNAMIC PROPERTIES OF Pd-Cd, Pd-In, Pd-Sn, AND Pd-Sb ALLOYS (K. M. MYLES AND J. B. DARBY, JR.)

Publications

J. B. Darby, Jr., R. Kleb, and O. J. Kleppa, *Twin Liquid Metal Solution Calorimeter*, Rev. Sci. Inst. **37**, 164 (1966).

J. B. Darby, Jr., *The Relative Heats of Formation of Solid Gold-Palladium Alloys*, Acta Met. **14**, 265 (1966).

J. B. Darby, Jr., K. M. Myles and J. N. Pratt, *Thermodynamic Properties of Pd-Cd and of Pd-Sb Alloys*, J. Metals **18**, 1162 (1966) [Abstract].

Previous studies on the thermodynamic properties of Pd-noble metal alloys (ANL-7000 and ANL-7155) indicate that substantial contributions to the thermodynamics of the systems, in particular the heats of formation, are derived from the relative changes in internal energy that result from the redistribution of electrons upon formation of the alloys. An extension of this work has included an investigation of the significance of the same contributions to the thermodynamic properties of polyvalent solutes in Pd. Accordingly, the heats of formation of the Pd-rich solid solutions of the Pd-Cd, Pd-In, Pd-Sn and Pd-Sb systems and the activities and free energies of formation in the Pd-Cd system were determined.

The activities and free-energies of the Pd-Cd alloys were calculated from the vapor pressure of cadmium over the alloys that was acquired by the dew-point method. This technique was selected after preliminary experiments with the torsion-effusion apparatus (ANL-6657) indicated that the diffusion rate of cadmium in the alloys was too low to maintain a constant effusion rate; a condition that resulted in the depletion of cadmium from the surface of the sample. The dew-point method has the intrinsic advantage of being reversible and, hence, independent of the diffusion rate.

The dew-point apparatus is illustrated in Figure 240. An evacuated quartz capsule that contains the specimen is enclosed in a gradient tube furnace. A port-hole near the top of the furnace permits a stereo-microscope to be focused onto the inside front wall of the capsule, which is the coldest region. Four fritted-quartz filter discs thermally separate the top of the capsule from the bottom.

46037

FIG. 240. A Schematic Diagram of the Dew-point Apparatus

In operation the temperature of the top of the capsule, which is maintained at temperatures where the vapor pressure of liquid cadmium, the vaporizing specie, is between 1 and 100 mm of Hg,⁽³³⁴⁾ is decreased until the dew point of cadmium is observed with the microscope. Simultaneous with the observation, the temperatures of the sample and of the cadmium condensate are obtained by means of Pt/Pt-10w/oRh thermocouples. The experiment is repeated at various sample temperatures until a vapor pressure versus reciprocal temperature relationship has been determined.

The high volatility of cadmium required that an elaborate procedure be employed to prepare the Pd-Cd alloys. A Cd-rich master alloy, which contained approximately 60a/oCd, was prepared in an induction furnace by dissolving palladium foil into liquid cadmium. The experimental alloys were subsequently produced by dropping predetermined quantities of the master alloy into aliquots of molten palladium. Unfortunately, the alloys with palladium concentrations less than 70 a/o were found to be heterogeneous. These were homogenized at 1200°C for two to three hours in evacuated quartz capsules that were enclosed in a stainless steel bomb under a pressure of approxi-

⁽³³⁴⁾ Fogler, M. F. and Rodebush, W. H., J. Amer. Chem. Soc. **45**, 2080 (1923).

45536

FIG. 241. The Activities of Cd at 1350°K.

45537

FIG. 242. The Activities of Pd at 1350°K.

mately eight atmospheres at room temperature. All of the alloys were heat treated at 1100°C for 10 days and their homogeneity was confirmed by X-ray analysis and optical metallography.

The activities of cadmium at 1350°K were computed from the vapor pressure data, with pure solid cadmium as the reference state,⁽³³⁵⁾ and are shown in

⁽³³⁵⁾ Aldred, A. T., Filby, J. D., and Pratt, J. N., Trans. Faraday Soc. **55**, 2030 (1959).

45535

FIG. 243. The Integral Heats of Formation at 298°K for the Pd-Ag, Pd-Cd, Pd-In, Pd-Sn, and Pd-Sb Alloys.

Figure 241. The extremely large deviations from ideality are in agreement with values recently obtained by other workers whose techniques involved chemical transfer and solid-electrolyte emf.⁽³³⁶⁾ The activity values of the ordered alpha-prime phase⁽³³⁷⁾ were also determined since the structure of this phase appears to be closely related to the primary alpha phase. The computed values of the activities of palladium are shown in Figure 242. The limits of the phase boundaries as defined by the activities are in very good agreement with those determined by metallographic and X-ray examination.

The heats of formation at 298°K, determined for the Pd-rich terminal solid solutions in the Pd-Cd, Pd-In, Pd-Sn, and Pd-Sb systems, are included in Figure 243. The heats of formation were calculated from heats-of-solution data obtained by means of a twin liquid-metal solution calorimeter, which is described in a publication listed above. The Pd-Cd samples were taken from the alloys prepared for the vapor-pressure experiments. The remaining alloys were prepared by an arc-melting technique and subsequently heat treated to ensure complete homogenization.

The free energies and the heats of formation for the Pd-Cd alloys are shown in Figure 244. For the primary solid-solution alloys the two quantities have large negative values of nearly equal magnitude. The free energies apparently are dominated by the heats of formation. However, in the ordered alpha-prime al

⁽³³⁶⁾ Pratt, J. N., private communication.

⁽³³⁷⁾ Hansen, M. and Anderko, A., *Constitution of Binary Alloys*, McGraw-Hill, New York (1958).

45993

FIG. 244. The Integral Free Energies of Formation at 1350°K and Integral Enthalpies of Formation at 298°K of Pd-Cd Alloys.

loys ($N_{Cd} > 0.39$) the free energy values continue to increase in magnitude while the heats of formation begin to decrease, which is a result of a change in entropy.

In general, the heats of formation of the alloy systems investigated appear to become more exothermic as the atomic number of the solute increases. For comparison, the heats of formation for the Pd-Ag⁽³³⁸⁾ systems are also plotted in Figure 243. When these data are plotted as a function of electron concentration, e/a , the values for the Pd-Cd, Pd-In, and Pd-Sn alloys fall, within the experimental error, on a common curve as shown in Figure 245. The magnitude susceptibilities versus e/a as shown in Figure 246 for the Pd-Ag, Pd-Cd, and Pd-Sb alloys has been interpreted in terms of a simple redistribution of electrons upon alloying.⁽³³⁹⁾ There is some evidence that Pd-Sn alloys also follow this behavior.⁽³⁴⁰⁾ The fact that both the heats of formation and the susceptibilities are a function of the electron concentration suggests that electronic contributions are dominant in the thermodynamic properties of the polyvalent alloys in a manner similar to the Pd-noble metal alloys.

Contrary to inferences based on susceptibility data the heats of formation of the Pd-Sb and the Pd-Ag alloys do not fall on a common curve. The heats of formation are relative measurements, that is, a function

45539

FIG. 245. The Integral Heats of Formation at 298°K for the Pd-Ag, Pd-Cd, Pd-In, Pd-Sn, and Pd-Sb Alloys as a Function of Electron Concentration.

43402

FIG. 246. The Spin Paramagnetic Susceptibilities of the d -conduction Electrons of Pd-Ag, Pd-Cd, and Pd-Sb Binary Alloys at 0°K as a Function of Electron-to-atom Ratio.

⁽³³⁸⁾ Hultgren, R., Orr, R. L., Anderson, P. D., and Kelly, K., *Selected Values of Thermodynamic Properties of Metals and Alloys*, John Wiley, New York (1963).

⁽³³⁹⁾ Lam, D. J., and Myles, K. M., *Phys. Soc. Japan* **21**, 1503 (1966).

⁽³⁴⁰⁾ Montgomery, H., private communication.

44049

FIG. 247. The Integral Heats of Formation for the Pt-Cu System.

of the state of the component elements, and are the sum of many contributions that originate from various sources. A tentative explanation for the smaller absolute values for the heats of formation of the Pd-Sb alloys may be the result of an endothermic contribution that arises from the presence of covalent bonds in pure antimony that must be broken upon alloying. The Pd-Sb results are more difficult to rationalize. The

larger ionic size of silver as compared with the other solutes studied suggests that an endothermic ionic-repulsion term might also be larger. Unfortunately, no satisfactory theoretical model is known that permits the calculation of the magnitude of this contribution.

c. THE HEATS OF FORMATION OF Pt-Cu ALLOYS (J. B. DARBY, JR.)

The determination of the heats of formation at 298°K for a series of alloys across the Pt-Cu system has been completed and the values are shown in Figure 247 together with the data for the copper-rich alloys at 913°K published by Oriani and Murphy.⁽³⁴¹⁾ Although the two sets of data were obtained at temperatures approximately 600° apart, the results are in good agreement. The observed differences in the heats of formation in the composition range of 0.55 to 0.85 mole fraction of copper probably reflect difference in the atomic configuration for the two sets of alloys. The three alloys investigated by Oriani and Murphy in this region were probably ordered according to the diagram published by Hansen and Anderko.⁽³⁴²⁾ Therefore, these alloys would be expected to be somewhat more exothermic than the alloys of the present investigation.

A paper will be submitted for publication in the near future on the thermodynamic properties of the Pt-Cu system that will summarize these results as well as those reported previously (ANL-7155).

⁽³⁴¹⁾ Oriani, R. A., and Murphy, W. K., *Acta Met.* **10**, 879 (1962).

⁽³⁴²⁾ Hansen, M., and Anderko, K., *Constitution of Binary Alloys*, McGraw-Hill, New York (1958).

4. Nuclear Magnetic Resonance Studies

a. INTERMETALLIC COMPOUNDS OF ALUMINUM WITH GROUP-VIII TRANSITION ELEMENTS (D. O. VAN OSTENBURG, J. J. SPOKAS,* AND C. H. SOWERS)

Publications

D. O. Van Ostenburg, J. J. Spokas, and C. H. Sowers, *The Knight Shift and Nuclear-Spin-Lattice Relaxation in FeAl, RuAl, and OsAl Intermetallic Compounds*, *Bull. Am. Phys. Soc.* **11**, 219 (1966) DD2.

J. J. Spokas, C. H. Sowers, and D. O. Van Ostenburg,

* Consultant to the Metallurgy Division, St. Procopius College.

NMR in Aluminum/Transition-Metal Compounds, *Bull. Am. Phys. Soc.* **11**, 482 (1966) FG. 7.

The intermetallic compounds FeAl, RuAl, OsAl, CoAl, RhAl, IrAl, and NiAl have ordered bcc or CsCl structures. At room temperature, the FeAl system exhibits the FeAl structure from 33 to 52a/oAl. The range for CoAl and NiAl is comparable. For RuAl, OsAl, RhAl, and IrAl alloys the corresponding structures are believed to exist over a similar range of compositions although the limits are not known. In the RuAl and OsAl systems marked negative deviations from Vegard law are observed in which there is a minimum in atomic mean volume at the 50-50 composition. This implies strong bonding of a charge transfer type and is mani-

fested in the brittleness of these compounds. The RuAl and OsAl compounds have a silver and pinkish-gold color, respectively, while FeAl is metallic gray. This is also suggestive of a charge transfer in which the aluminum contributes its outer electrons to ruthenium and osmium, resulting in the electronic configurations of silver and gold. This study was initiated in order to examine the electronic and structural properties of the compounds by means of wide-line and pulsed nmr. The systems are metallic with a positive temperature coefficient of resistivity and at room temperature, e.g., the resistivity of OsAl is $\approx 19 \mu\Omega\text{cm}$.

The Al Knight shift, K , in the six cubic compounds, excluding FeAl, falls between -0.033% for RuAl and $+0.055\%$ for NiAl. The nuclear-spin-lattice relaxation time, T_1 , at room temperature lies in the range 0.10 sec for NiAl and 2.93 sec for IrAl. In CoAl the cobalt relaxation time is nearly 100 times shorter than the aluminum relaxation time.

It is found that $T_1 T \approx \text{const.}$ from room temperature to 77°K for each alloy indicating that the predominant relaxation path is via conduction electrons. However, at 4.2°K , $T_1 T$ is more than a factor of two lower and the recovery of the magnetization does not follow a simple exponential curve. Thus, at low temperatures there appears to be another mechanism contributing to the relaxation, the cause of which is not known.

The measured relaxation time and Knight shift can be studied via a "generalized Korringa" relation $\gamma_N^2 T_1 T K_{\text{meas}}^2 = \text{constant}$, where γ_N is the nuclear gyromagnetic ratio. Systems that have similar electronic band characteristics should give similar contributions to the contact, core polarization and orbital terms in the shift and relaxation rate; and therefore should yield essentially the same constant. For example, in FeAl, RuAl, and OsAl the constant is respectively 1480, 510 and $540 \text{ sec}^{-1} \text{Oe}^{-2} \text{K}$. Thus, RuAl and OsAl might have similar bands quite different from FeAl.

Assuming that the relaxation rate in RuAl and OsAl is governed primarily by the s -electrons allows one to calculate the fraction of the shift due to s -electrons, K_s , from the regular Korringa equation, $\gamma_N^2 T_1 T K_s^2 = \hbar^2 \gamma_e^2 / 4\pi k$, where γ_e is the gyromagnetic ratio of the electrons, k is Boltzmann's constant, and $\hbar$ is Planck's constant divided by 2π . We find

$$K_{s\text{Al in RuAl}} = +0.023\% \quad \text{at } 300^\circ\text{K}$$

$$K_{s\text{Al in OsAl}} = +0.017\% \quad \text{at } 300^\circ\text{K}$$

The aluminum Knight shift K_s is proportional to the product of the density of states at the Fermi level and the fractional s -character on the aluminum sites of the states averaged over the Fermi surface. Consequently, a small K_s can be due to the smallness of either

of these quantities. [The K_s value in pure aluminum is $+0.162\%$.] Under the assumption that the d -bands are filled in these compounds we can assume that their electronic specific heat is close to that of pure aluminum. This is corroborated by the specific heat of NiAl, which is 87% that of pure aluminum. This leads to the conclusion that the small shifts are due to a lack of s -character at the aluminum sites. To be more specific, a tight binding calculation reveals that there is little s -character in the wave functions at the Fermi level associated with the aluminum sites.

The line-widths of all the samples exceed that due to dipolar coupling among nuclei and, despite the cubic symmetry of the compounds and a post-filing anneal, also show a quadrupolar line-width contribution. The excess width in FeAl has been attributed by Seitchik et al.⁽³⁴³⁾ to inhomogeneous Knight-shift broadening from the Ruderman-Kittel-Yosida mechanism. The excess width in the other compounds is believed due to first-order quadrupolar effects since following a 90-30 pulse sequence a quadrupolar echo is observable even in the annealed samples. Of course, T_1 broadening is ruled out because of the large values of these relaxation times.

The outer-electron configurations of the neutral atoms of Fe, Ru, and Os in their ground states are compared with those of Cu, Ag, and Au in the following:

Fe $3d^6 4s^2$	Cu $3d^{10} 4s$
Ru $4d^7 5s^1$	Ag $4d^{10} 5s$
Os $5d^6 6s^2$	Au $5d^{10} 6s$

Line positions are explained by postulating a certain amount of charge transfer from aluminum, configuration $3s^2 3p$, to the transition metal d -band.

It is possible that for atoms with unfilled d -shells, there is an exchange polarization of the inner shell s -electrons such as to produce at the nucleus a field opposed to the applied field and consequently a shift of opposite sign to that usually obtained in metals. Assuming that the exchange polarization is also effective at the aluminum nucleus the negative shift in FeAl is plausible since iron requires 4 electrons to fill its $3d$ shell and aluminum can supply only 3.

Ruthenium requires only 3 electrons and so in RuAl the d -band is filled. This implies small s -character remaining on the aluminum site (corroborated by our K and T_1 measurements) and that this compound has the silver electronic configuration.

Osmium requires 3 electrons if one of its $6s$ electrons also goes into the d -band. This again implies small

(343) Seitchik, J. A., and Walmsley, R. H., Phys. Rev. **137A**, 143 (1965).

s-character remaining at the aluminum site (corroborated by our K and T_1 measurements) and that this compound has the gold electronic configuration.

These results suggest that in the CsCl-type structure of aluminum with the group-VIII transition elements that there is considerable charge transfer from aluminum to the transition metal. Thus, the distinction between metals and ionic crystals is beginning to lose its clear-cut character. It appears that for intermetallic compounds bonding of a type intermediate between ionic and metallic is in vogue. It is our aim to more fully elucidate these concepts through the use of nmr and related phenomena.

b. VANADIUM-IRON ALLOYS (D. O. VAN OSTENBURG, C. H. SOWERS, AND J. J. SPOKAS)

Publication

D. O. Van Ostenburg, C. H. Sowers, and J. J. Spokas, *Nuclear-Spin-Lattice Relaxation of V^{51} in V-Fe Alloys*, Physics Letters **20**, 461 (1966).

The V^{51} nuclear-spin-lattice relaxation time has been measured from pure vanadium up to V-40a/oFe. The composition dependence of the relaxation rate closely resembles the term linear in temperature in the low-temperature specific heat and shows a second peak near 34a/oFe. The data imply that the composition dependence of the relaxation rate is governed by the composition dependence of the d -density of states for this alloy system. A more detailed account of this work may be found in the above publication.

c. β -MANGANESE (G. A. MATZKANIN AND D. O. VAN OSTENBURG)

The nuclear-spin-lattice relaxation time T_1 has been measured in β -Mn from 4.2°K to room temperature. The relaxation time had previously been measured from 1.5 to 77°K by Masuda et al.,⁽³⁴⁴⁾ although there is reason to believe that these measurements might be in error due to the presence of ferromagnetic nitrides

⁽³⁴⁴⁾ Masuda, Y., Asayama, K., and Kobayashi, S., J. Phys. Soc. Japan **19**, 460 (1963).

formed during the process of crushing the sample in air.⁽³⁴⁵⁾ Recently, Drain has carefully examined the NMR parameters from 140 to 340°K with samples crushed in an argon atmosphere,⁽³⁴⁶⁾ and finds some differences with respect to earlier NMR measurements using air-crushed samples.⁽³⁴⁷⁾ These events have prompted us to repeat the earlier T_1 measurements of Ref. 345 and to extend them to room temperature using a sample crushed in an argon atmosphere.

The spin-lattice relaxation time T_1 is found to increase from about 0.89 msec at room temperature to about 1.66 msec at 4.2°K while T_1T , which is usually constant for simple s-electron relaxation mechanisms, changes by two orders of magnitude in this temperature range. The value of $T_1T = 7$ msec-°K at 4.2°K agrees very well with the results of Ref. 345 at this temperature, however, these authors ignored deviations of T_1T at the higher temperatures. The change in T_1T is roughly linear from room temperature down to 140°K, and then falls off rapidly to its value at 4.2°K. The rapid change in T_1T below 140°K is thought possibly to be related to changes in the NMR line shape reported by Drain and to the disappearance of quadrupole satellites below this temperature. The strong temperature dependence of T_1T indicates that relaxation due to the s-conduction electrons is not important in β -Mn but rather that the d -electrons contribute significantly to the relaxation rate.

Intensity measurements of the Bloch decay amplitude referenced to the signal in aluminum metal indicates that only the manganese atoms of type I of the two crystallographically nonequivalent sites contribute to the observed resonance as has also been reported by Drain.⁽³⁴⁶⁾ Continuous wave measurements of the NMR line width at various temperatures and values of magnetic field also agree well with Drain's recent work.

⁽³⁴⁵⁾ Butterworth, J., Drain, L., and Penfold, J., Phys. Letters **15**, 215 (1965).

⁽³⁴⁶⁾ Drain, L., Proc. Phys. Soc. **88**, 111 (1966).

⁽³⁴⁷⁾ Jaccarino, V., Peter, M., and Wernick, J. H., Phys. Rev. Letters **5**, 53 (1960).

G. THEORETICAL STUDIES OF DILUTE ALLOYS

1. Knight Shift in Dilute Silver Alloys (L. C. R. ALFRED AND D. O. VAN OSTENBURG)

Friedel and his co-workers⁽³⁴⁸⁾ have developed a free-electron theory of Knight shift in dilute alloys. In this theory the change in the Knight shift with solute concentration is given by the relation:

$$\frac{\langle \Delta K \rangle_{av}}{K_0 c} = \sum_l [A_l \sin^2 \eta_l + B_l \sin 2\eta_l]. \quad (1)$$

where $\langle \Delta K \rangle_{av}$ is the change in the Knight shift averaged over the lattice, K_0 is the Knight shift of the solvent, c is the solute concentration, η_l is the phase shift of the l th order partial wave for electrons at the Fermi level, and A_l and B_l are quantities defined by the lattice sums:

$$A_l = (2l + 1) \sum_i [n_i^2(k_F R_i) - j_l^2(k_F R_i)],$$

and

$$B_l = -(2l + 1) \sum_i j_l(k_F R_i) n_l(k_F R_i);$$

with k_F denoting the Fermi wave number of the solvent, R_i a lattice vector, and j_l and n_l the spherical Bessel and Neumann functions, respectively.

For an estimate of the right side of Equation (1), i.e. the relative average Knight shift per a/o of solute (aks), the phase shifts can either be obtained from the literature on the electronic structure of dilute alloys or be evaluated by standard methods of scattering theory.⁽³⁴⁹⁾ No accurate estimates of the Knight shift coefficients, A_l and B_l , however, are available and it will be the object of the present investigation to carry out these calculations and to compare the results with previous estimates.

Since the Knight-shift coefficients depend only on $k_F R_i$, they are, in a free electron model, constants for metals of the same valence and structure. Previous estimates of these constants were carried out by Rowland⁽³⁵⁰⁾ and Daniel⁽³⁴⁸⁾ in their work on the interpretation of Knight shift data in dilute silver alloys. Rowland carried out the lattice summation to 15 atomic shells, while Daniel summed up to the 8th shell and accounted for the rest of the lattice by a bulk integral on the assumption that the lattice distribution can be averaged into a continuum of constant density. Although both

Rowland and Daniel obtained fair agreement with experiment, their results have to be taken with reservation because no valid criterion was adopted either by Rowland in deciding at which shell the contribution of the rest of the lattice becomes negligible or by Daniel in determining after which shell it is a good approximation to average the lattice distribution. Since the quantity to be summed behaves asymptotically as an undamped sinusoidal function, it is clear that (1) a convergence criterion is not directly applicable and (2) averaging the distribution too early can mask an important coupling effect between the discrete lattice and the Bessel functions. To resolve these uncertainties it was decided to carry out an evaluation of these constants by the methods adopted by Daniel and by Rowland but extending the region of lattice summation to several hundred shells so as to examine more closely

45960

FIG. 248. Plot of Knight Shift Coefficients for a Monovalent fcc Metal as a Function of $k_F R$.

⁽³⁴⁸⁾ Blandin, A., Daniel, E., and Friedel, J., *Phil. Mag.* **4**, 180 (1959); Blandin, A., and Daniel, E., *J. Phys. Chem. Solids* **10**, 126 (1959).

⁽³⁴⁹⁾ See, for example, Messiah, A., *Quantum Mechanics*, Chapt. X, Interscience Publishers, Inc., New York (1961).

⁽³⁵⁰⁾ Rowland, T. J., *Phys. Rev.* **125**, 459 (1962).

TABLE 93. VALUES OF $-\langle\Delta K\rangle_{11}/K_0c$, THE AVERAGE KNIGHT SHIFT PER a/o OF SOLUTE, IN Ag ALLOYS

Ag Alloys	Experi- mental ^(a)	Calculations Using Blatt's Phase Shifts ^(b)		Calculations Using G.H.V.'s Phase Shifts ^(c)	
		Pres. Calc.	Row- land ^(a)	Pres. Calc.	Row- land ^(a)
Cu	0.07	0.02	0.01		
Zn	0.35	0.09	0.14		
Cd	0.36	0.11	0.16	0.54	0.77
Ga	0.62	0.66	1.02		
In	0.60	0.55	0.84	0.14	0.41
Ge	0.82	1.16	1.56	1.54	2.35
Sn	0.82	1.04	1.5	1.46	2.20
As	0.76	0.98	1.28		
Sb	1.09	1.01	1.37	2.24	3.08

^(a) T. J. Rowland, Phys. Rev. **125**, 459 (1962).

^(b) F. J. Blatt, Phys. Rev. **108**, 285 (1957).

^(c) C. A. Giffels, G. W. Hinman, and S. H. Vosko, Phys. Rev. **121**, 1063 (1961).

their variation with the number of terms considered in the sum. The curves obtained for the Knight shift coefficients of the first order for increasing $k_F R$ and number of shells are shown in Figure 248. The curves for the higher order coefficients exhibit the same general features as those for $l = 0$. The correct value of the coefficients in each case is the mean of the tail of the curve; and it is clear that one has to sum out to at least 200 shells to arrive at a fair estimate of this mean value. It is also obvious from the figure that terminating the lattice sums at the ~ 8 th or ~ 15 th shell, as did the previous authors, will yield values with a relatively wide error margin. The Knight shift coefficients derived from these curves were utilized to evaluate the aks for dilute silver alloys by application of phase shifts employed by Rowland. The results are given in Table 93 where the experimental data and the theoretical estimates of Rowland are shown for comparison. The overall agreement with experiment is improved quite significantly when the correct coefficients are used.

2. A New Scheme for the Construction of Phase Shifts with Application to NMR (L. C. R. ALFRED AND D. O. VAN OSTENBURG)

An important characteristic of the redistribution of conduction electrons around a point defect in a metal

45994

FIG. 249. The fractional Knight Shift Change for Unit Solute Concentration, $K^{-1}\partial K/\partial c$, for Various Impurities in Monovalent Metals. Data points are denoted by $\bullet$. Curves denote theoretical values using different sets of phase shifts, ---- B , -.-.- KV , and — the new set.

(e.g. metal B dissolved substitutionally in metals) is the phase shift at the Fermi level in the partial wave scattered by the perturbing defect potential. For a dilute concentration of impurities this scattering potential is almost spherically symmetrical and the phase shift in the l th order solution of the radial Schrödinger equation is denoted by η_l . Phase shifts play an important part in the study of dilute alloys properties that depend on the asymptotic form of the scattered wave and these phase shifts must be determined accurately to several wave orders for useful application to these problems. Currently, there are two sets of estimated values of phase shifts in extensive use in resonance work: one, B , proposed by Blatt,⁽³⁵¹⁾ is based on a square well potential, the other, KV , due to Kohn and Vosko,⁽³⁵²⁾ who utilized resistivity data and the Friedel sum rule, is derived semiempirically. The former theory has been criticized for adopting an arbitrary form for the solute potential and the second for giving phase shifts only to $l = 1$. By combining the semiempirical approach of KV with the Born approximation, we have obtained a scheme for generating a new set of phase shifts of unlimited order that lead to better agreement with Knight-shift data in liquids.

⁽³⁵¹⁾ Blatt, F. J., Phys. Rev. **108**, 285 (1957).

⁽³⁵²⁾ Kohn, W., and Vosko, S. H., Phys. Rev. **119**, 912 (1960).

copper⁽³⁵³⁾ and solid silver⁽³⁵⁴⁾ alloys than obtained previously. The results for liquid copper alloys are shown in Figure 249. The marked improvement between

⁽³⁵³⁾ Odle, R. L., and Flynn, C. P., *Phil. Mag.* **13**, 699 (1966).

⁽³⁵⁴⁾ Rowland, T. J., *Phys. Rev.* **125**, 459 (1962) and Van Ostenburg, D. O., and Alfred, L. C. R., *Bull. Am. Phys. Soc.* **11**, 916 (1966) X2.

theory and experiment is at once apparent. These calculations show that the free-electron theory of screening of electrons about solute sites in monovalent metals can be used to predict the relative change in Knight shift versus various valent solute additions provided suitably chosen phase shifts are used. This work is continuing and will be extended to quadrupole effects and polyvalent solvents.

H. PHYSICAL CERAMICS RESEARCH

1. Chemical Potentials and Sintering of Pure Metals and Impure Ionic Compounds

(D. W. READEY)

Publications

D. W. Readey, *Chemical Potentials and Initial Sintering in Pure Metals and Ionic Compounds*, J. App. Phys. **37**(6), 2309-2312 (1966).

D. W. Readey, *Mass Transport and Sintering in Impure Ionic Solids*, J. Am. Cer. Soc., **49**(7), 366-369 (1966).

The purpose of this completed study was to provide a firmer theoretical foundation for diffusion-controlled sintering in pure and impure ionic solids. The procedures used in the study, and the conclusions, which were summarized in the 1965 Annual Progress Report (ANL-7155), were fully reported in the two above publications.

2. Transport Processes in Ionic Oxides (D. W. READEY AND R. E. JECH)

As was discussed briefly in the 1965 Annual Report (ANL-7155), the purpose of this study is to investigate ionic transport processes in well-defined oxide systems with the hope of generating data amenable to theoretical analysis. Unfortunately, most of the data in the literature dealing with this subject are of questionable value because of the lack of information concerning impurity concentration, its oxidation state and distribution. Since the task of preparing oxide materials of sufficient purity to study intrinsic transport processes is indeed formidable, it was decided to study a system in which the impurity content and its effect on the defect concentration and resulting transport processes could be determined. The ionic conductivity of calcium oxide (CaO) doped with gadolinia (Gd_2O_3) was to be investigated. If Gd_2O_3 forms substitutional solid solutions with CaO, then for each two Gd^{+3} ions in solution there should exist a Ca^{+2} vacancy. Hence, the ionic conductivity should be proportional to the Gd_2O_3 concentration in solid solution. Gadolinia was chosen as the solute since the Gd^{+3} ionic radius is similar to that of calcium, the Gd^{+3} ion is the only known oxidation state (therefore, the ambient oxygen pressure should have no effect on the defect concentration), and preliminary information⁽³⁵⁵⁾ indicates a reasonable amount of solubility of Gd_2O_3 in CaO.

Solubility of Gd_2O_3 in CaO

The solid solubility of Gd_2O_3 in CaO has been determined and is given in Figure 250. The solid solubility was determined by the change in lattice parameter of

⁽³⁵⁵⁾ Barry, T. L., Thesis, Pennsylvania State University, 1964.

CaO with Gd_2O_3 content and the results agree well with earlier data.⁽³⁵⁵⁾ The lattice parameters were determined from the $CuK\alpha$ and $CuK\beta$ lines in the back-reflection region of powder patterns with a least-squares lattice-constant computer program.⁽³⁵⁶⁾ Since the total change in lattice parameter over the range of solubility is only one part in 10^3 , the probable errors in solubility are fairly large.

The solid solutions were prepared by precipitating the oxalates from nitrate solutions, calcining, pressing, and sintering at 1600°C for 20 hours. A typical microstructure is shown in Figure 251. For the X-ray measurements, the sintered material was pulverized and sieved. Gadolinium concentrations determined by wet chemical analysis were within five percent of those calculated on the basis of the nitrate solutions.

The abrupt change in the solubility curve around 1270°C is near the monoclinic-cubic transformation temperature of Gd_2O_3 .⁽³⁵⁷⁾ This transformation is extremely sluggish⁽³⁵⁷⁾ and from the X-ray data in the two-phase region it could not be determined whether or not the Gd_2O_3 phase present was the equilibrium phase for that temperature. Hence, the solubility curve below 1300°C may not represent true equilibrium between Gd_2O_3 and CaO solid solutions.

Density of Solid Solutions

In order to show that solution of Gd_2O_3 takes place with the formation of cation vacancies, the densities

⁽³⁵⁶⁾ Mueller, M. H., Heaton, L., and Miller, K. T., A Cryst. **13**, 828 (1960).

⁽³⁵⁷⁾ Stecura, S., U. S. Bureau of Mines Report No. RI-6616, 1965.

of the solid solutions were measured and compared with those calculated from the measured lattice parameter on the basis of both interstitial oxygen and cation vacancies. The results are given in Figure 252 as the difference in density between the pure CaO and the solid solutions. Since the densities were measured with

45972

FIG. 250. Solubility of Gd_2O_3 as a Function of Temperature. The error bars represent probable errors.

45977

150X

FIG. 251. Microstructure of 2m/o Gd_2O_3 Solid Solution Sintered at 1600°C for 20 Hours and Air-Cooled.

45973

FIG. 252. Density Differences between Pure CaO and Gd_2O_3 -CaO Solid Solutions as a Function of Gd_2O_3 Concentration Calculated from Measured Lattice Parameters for the Interstitial Oxygen and Cation Vacancy Models, and the Measured Values.

powdered material in a liquid pycnometer, systematic errors inherent in the technique are minimized by plotting the density difference. Although the agreement is not perfect, the evidence strongly indicates the formation of calcium vacancies. The greater deviations at the higher concentrations may reflect the difficulty of retaining the solid solution phase during quenching.

Electrical Conductivity

Preliminary AC electrical conductivity measurements have been made at 10 Kc in the solid-solution region from about 1000 to 1625°C in air. The observed activation energy for conductivity is close to 50 kcal/mole. Theoretically, the ionic conductivity, σ , is given by:⁽³⁵⁸⁾

$$\sigma = \frac{na^2(ze)^2\nu}{kT} \exp\left(-\frac{\Delta H_m}{kT}\right) \quad (1)$$

where

n = number of vacancies per unit volume

a = nearest neighbor cation distance

ze = cation charge

⁽³⁵⁸⁾ Lidiard, A. B., in *Handbuch der Physik*, edited by S. Flugge (Springer-Verlag, Berlin, 1956), Vol. XX.

ν = cation vibration frequency

k = Boltzmann's constant

T = absolute temperature

ΔH_m = activation energy for cation jump.

With the observed activation energy, for the $1m/oGd_2O_3$ solid solution at $1600^\circ C$, the conductivity calculated from Equation (1) is $1.4 \times 10^{-6} \text{ ohm}^{-1} \text{ cm}^{-1}$. The ob-

served conductivity at the same temperature is about $5 \times 10^{-6} \text{ ohm}^{-1} \text{ cm}^{-1}$ which agrees quite favorably with the calculated value. Also, preliminary results indicate increasing conductivity with increasing Gd_2O_3 concentration. At the present time, experiments are under way to more fully delineate the temperature and Gd_2O_3 concentration dependence of the conductivity.

3. Grain-Boundary Energies of Oxides (D. W. READEY AND R. E. JECH)

Boundary Energies

The intent of this program is to study the energies of grain boundaries in oxides as a function of crystallographic misorientation across the boundary, temperature, impurity concentration, etc. The technique used, consists of measuring the dihedral angle, θ , at the root of the groove formed at the intersection of the boundary with the free surface during annealing. The relative boundary energy, λ_b , is given by

$$\lambda_b = 2\lambda_s \cos \theta/2, \quad (1)$$

where λ_s is the energy of the free surface. The entire groove profile is reproduced at a magnification of $10,000\times$ to $100,000\times$ by means of a modified surface profilometer. A typical groove profile, as obtained, is shown in Figure 253. This apparatus affords at least an order of magnitude improvement over previous methods in the accuracy with which the groove angle can be measured.

The initial boundary energy measurements were made with NiO bicrystals because of their ease of fabri-

cation and orientation, and because reasonably well-behaved (no surface faceting during annealing) grooves can be obtained. A photomicrograph of a typical groove formed during annealing in air is shown in Figure 254. The NiO bicrystals are made in an arc-image furnace by forming a molten boule on two approximately-oriented NiO single crystals. Upon slow cooling of the boule, a bicrystal of sufficient size ($\sim 5 \text{ mm}$ diameter usually) is formed. A surface perpendicular to the boundary plane is then ground and polished and Laue patterns are taken on both sides of the boundary to accurately determine the crystallographic misorientation across the boundary. Pure tilt boundaries up to about 50 degrees misorientation have been prepared and energy measurements made at $1535^\circ C$ in air indicate that the boundary energy rises quickly with misorientation to about $0.8 \lambda_s$ and then remains fairly constant. Further experiments are in progress to establish the misorientation dependence more precisely and to look for any effect of annealing temperature.

Grooving Kinetics

Mullins^(359,360) has developed the theory of the kinetics of grain-boundary grooving whereby the mechanism of groove formation (surface or volume diffusion, evaporation and condensation) can be determined from the size and shape of the groove profile (see Figure 253) as a function of time. Here again, the apparatus to obtain groove profiles used in this study is far more accurate than previous methods for determining grooving kinetics. Preliminary data indicate, at $1535^\circ C$ in air, the grooves on NiO are formed by a combination of a diffusion process and vaporization and condensation. The experiments on grooving kinetics are also continuing.

Etch-Pit Observations on NiO

In order to study the perfection of the NiO bicrystals and the damage done to the surface by the profilometer

45974

FIG. 253. Actual Measured Profile of a Boundary Groove Formed during Annealing of an NiO Bicrystal. Note the "humps" on either side of the groove indicating that either volume or surface diffusion is contributing to groove growth.

⁽³⁵⁹⁾ Mullins, W. W., *J. Appl. Phys.* **28**, 333 (1957).

⁽³⁶⁰⁾ Mullins, W. W., *Trans. AIME*, **218**, 354 (1960).

45978

213×

FIG. 254. Grain Boundary Groove on 27° Tilt NiO Bicrystal After 100 hr at 1535°C in Air Oblique lighting.

45979

1000×

FIG. 255. As-cleaved NiO Single Crystal (100) Surface Etched 20 min in Boiling HNO₃.

45980

1000×

FIG. 256. Single Crystal NiO (100) Surface Etched 20 min in Boiling HNO₃ after Thermal Polishing at 1535°C for 20 hr in Air.

45976

1000×

FIG. 257. Interference Micrograph of Etch Pits on NiO Etched 70 min in Boiling HNO₃. Fringe spacing is 0.27 micron.

a dislocation etch procedure has been developed for NiO. An etch of boiling concentrated HNO_3 ($\sim 118^\circ\text{C}$) has been reported⁽³⁶¹⁾, but no suitable chemical polish, and HNO_3 -etched surfaces of as-cleaved NiO crystals have a very mottled appearance with a nonuniform pit size as shown in Figure 255. Experiments are under way to determine the cause of this etching behavior. However, it was found that NiO surfaces could be thermally polished ($\sim 1500^\circ\text{C}$ for several hours in air)

⁽³⁶¹⁾ Takeda, T., and Kondoh, H., *J. Phys. Soc. Japan*, **17**, 1315 (1962).

and subsequent etching with boiling HNO_3 produced well-defined etch pits whose size could be easily controlled as shown in Figure 256. The etch-pit size was found to be linear with time and interference micrographs, such as Figure 257, show that the shape also is invariant. The edges of the pits are parallel to $\langle 100 \rangle$ directions and the faces of the pits lie very close to the (510) planes of NiO. The etch procedure does not distinguish between fresh and aged dislocations but by careful inspection of pit shape, screw and edge dislocations can be distinguished.

4. Defect Equilibria in Nonstoichiometric Oxides (M. L. VOLPE AND J. F. REDDY)

The investigation of defect equilibria in nickel oxide was started this year with the construction of apparatus for making simultaneous measurements of diffusion and electrical conductivity at temperatures up to 1500°C . Nickel oxide monocrystals were prepared by both the Verneuil process in an arc-image furnace and by vapor decomposition. In addition, initial measurements have been made of both nickel and oxygen self-diffusion and electric conductivity.

Spectrographic analysis showed that the Verneuil crystals had identical impurity contents and that the minimum purity was 99.4%. Single-crystal wafers about one cm^2 in area and from 20 to 200 microns thick were also prepared by the vapor-phase reaction between water and NiBr_2 for future investigations of the effect of nonstoichiometry on optical absorption.

Electrical Conductivity of $\text{NiO}_{(1+x)}$

Conductivity measurements were made by the conventional "4-point probe" method,⁽³⁶²⁾ with the probes in the form of four Pt-Rh wires wrapped around a single crystal of NiO. For experiments made concurrently with nickel self-diffusion, a Pt-Rh wire cradle held the diffusion sample close to the conductivity sample. A flowing-gas atmosphere was used, consisting of tank oxygen for runs at one atmosphere and of either pure CO_2 or argon-oxygen mixtures for runs at a pressure lower than one atmosphere.

The conductivity of nickel oxide was measured over a range of temperature and oxygen pressure, with results very similar to those reported by Mitoff.⁽³⁶²⁾ Figure 258 presents our results for one atmosphere pressure (individual points) compared with Mitoff's (straight lines). Our data fit his lines remarkably well. Furthermore, we found at low temperatures the same

apparent slow attainment of equilibrium that he observed. The points in Figure 258 were obtained by stepwise change in temperature; above about 1000°C , equilibrium was attained within 15 minutes. Below 1000° this time interval was not sufficient for equilibrium, and the points followed curve E-F. Upon keeping the temperature at 897°C (point C) overnight, the conductivity dropped from $0.318 \text{ ohm}^{-1} \text{ cm}^{-1}$ (the point directly above C in Figure 258) to $0.175 \text{ ohm}^{-1} \text{ cm}^{-1}$, and did not change thereafter. Further decrease of temperature at 15 minute intervals produced the points on line C-D.

Our findings on the relationship between oxygen pressure and conductivity are displayed in Figure 259. We observe a $1/4$ -power dependence of conductivity on oxygen pressure. [The "activation energy" calculated from Figure 259, 22.7 kcal/mole, agrees well with 23.3 kcal/mole, the value calculated from the high-temperature line in Figure 258.] Thus, we conclude that reaction of oxygen with NiO takes place according to the equation:

rather than

Where O_i represents an oxygen ion in its proper lattice position, P_{O_2} is the oxygen pressure, $\oplus$ is an electron hole, and V_{Ni}^- and V_{Ni}^- represent nickel ion vacancies. All charges are relative to the lattice.

Nickel Self-diffusion in $\text{NiO}_{(1+x)}$

A sectioning method is being used to obtain the nickel self-diffusion coefficients. Nickel-63 is deposited

⁽³⁶²⁾ Mitoff, S. P., *J. Chem. Phys.* **35**, 882 (1961).

46042

FIG. 258 Comparison with Mitoff's (Ref. 362) Conductivity Data.

on the NiO diffusion samples (dimensions: 1 cm x 1 cm x 0.2 cm) by vacuum evaporation, after which it is oxidized to NiO in air at 600°C. Diffusion anneals of about 100 hours have been made after which the concentration of Ni⁶³ was determined as a function of penetration distance by grinding off layers ~10 microns thick parallel to the deposition plane and successively measuring the radioactivity that remained in the sample. The diffusion conditions closely approximated the diffusion of a planar source into a semi-infinite medium, so that the concentration of Ni⁶³ as a function of time, t , and penetration distance, x , was accurately given by:⁽³⁶³⁾

$$C(x,t) = M(\pi Dt)^{-1/2} \exp [-x^2/4Dt] \quad (3)$$

Where M is the amount initially deposited, and D is the self-diffusion coefficient. In determining the Ni⁶³ concentration by its radioactivity, a correction had to be made for the radiation that penetrated from the interior; because Ni⁶³ radiation is very weak, Equation (3) may be readily modified to give:^(364, 365)

⁽³⁶³⁾ Crank, J., *The Mathematics of Diffusion*, Clarendon Press, Oxford, 1956, p. 11.

⁽³⁶⁴⁾ Choi, J. S., and Moore, W. J., *J. Phys. Chem.* **66**, 1308 (1962).

⁽³⁶⁵⁾ Seibel, G., *Int. J. Appl. Rad. and Isotopes*, **15**, 679 (1964).

$$A_j[1 + x_j/2\mu Dt] = A(\pi\mu Dt)^{-1/2} \exp [-x_j^2/4Dt] \quad (4)$$

Here A_j is the measured residual activity at the penetration depth x_j , μ is the absorption coefficient for the radiation, and the other quantities are the same as in Equation (3). Since the correction term, $x_j/2\mu Dt$, was about 0.01, only an approximate value was needed for μ , and a method of successive approximations could be used to find the term on the left of Equation (4). A plot of $\log \{A_j[1 + a]\}$ (where $a_j = x_j/2\mu Dt$) vs. x_j^2 should be linear, and its slope would give the diffusion coefficient, D .

We have measured the self-diffusion of nickel in nickel oxide at one atmosphere oxygen pressure and 1198°C, and at 1.3×10^{-4} atmospheres and 1190°C. Our data are listed in Table 94, where it can be seen that a pressure dependence exists, the lower pressure run having the smaller diffusion coefficient.

46043

FIG. 259. Electrical Conductivity of NiO_{G+x} vs Oxygen Pressure. Upper curve T = 1205°C, lower curve T = 1056°C.TABLE 94 Ni SELF-DIFFUSION COEFFICIENT AS A FUNCTION OF P_{O_2}

Sample Number	T(°C)	P(atm)	D(cm²/sec)
6	1198	1	3.84×10^{-11}
5	1198	1	3.12×10^{-11}
7	1190	1.3×10^{-4}	1.15×10^{-11}

46041

Fig. 260. Penetration Plots for Ni Self-diffusion in $\text{NiO}_{(1+x)}$. $P = 1 \text{ atm.}$, $T = 1198^\circ\text{C}$.

Two diffusion samples 5 and 6 were used in the one atmosphere run. The small discrepancy between these two samples was probably due to a sectioning error that was known to occur with sample 6. According to calculations available in the literature,⁽³⁶⁶⁾ an error of this type would account for our observed difference in D values.

The penetration plots from which the diffusion coefficients were obtained were quite linear (see Figures 260 and 261), indicating that possible causes of error, such as poor approximation to the boundary conditions, lack of equilibrium with the surroundings, and the existence of surface diffusion were absent.

Oxygen Self-diffusion in $\text{NiO}_{(1+x)}$

Oxygen self-diffusion was measured with the method and apparatus described by W. K. Chen in last year's

⁽³⁶⁶⁾ Shirn, G. A., Wajda, E. S., and Huntington, H. B., *Acta Met* **1**, 513 (1953).

46040

Fig. 261. Penetration Plot for Ni Self-diffusion in $\text{NiO}_{(1+x)}$. $P = 1.3 \times 10^{-4} \text{ atm.}$, $T = 1190^\circ\text{C}$.

annual report (ANL-7155) and in the present report on page 276. The method consists of measuring the decrease of O^{18} content with time, of gas kept in contact with the diffusion sample. For these studies, NiO single-crystal wafers were used. They were 280 microns thick and were ground flat and parallel to about 2 microns. For oxygen pressures on the order of one atmosphere, O^{18} in the form of O_2^{18} was used; for lower pressures, of about 10^{-3} atmospheres, CO_2^{18} was used.

One measurement of the oxygen self-diffusion coefficient has been made at 1400°C and 0.25 atmosphere pressure, and one is in progress at 1400°C and 10^{-3} atmospheres. The high-pressure diffusion coefficient was found to be $1.2 \times 10^{-12} \text{ cm}^2/\text{sec}$, which compared favorably with the published value of $8.2 \times 10^{-13} \text{ cm}^2/\text{sec}$.⁽³⁶⁷⁾ We plan to continue these measurements of oxygen diffusion as a function of pressure and temperature at the same time that similar experiments are carried out on nickel diffusion.

⁽³⁶⁷⁾ O'Keeffe, M., and Moore, W. J., *J. Phys. Chem.* **65**, 1438 (1961).

5. Statistical Model of Partially Ordered Defects in MO_{2-x} (L. M. ATLAS)

Publication

L. M. Atlas, *Statistical Model for Oxygen Vacancies and Reduced Cations in a Fluorite Lattice*, Am. Ceram. Soc. Bull., **45** No. 4, 379 (1966) (Abstract).

A statistical model has been developed to account for the ordering of defects in hypostoichiometric, fluorite-type, metal-oxides. In this model, which represents a synthesis and elaboration of analyses by Rees⁽³⁶⁸⁾ and by Speiser and Spretnak,⁽³⁶⁹⁾ consideration has been given to the nonrandom distributions of anion vacancies and reduced cations (the latter are formed when electrons dissociated from the vacancies are trapped at cation sites).

An assumption in the theory is that ordering occurs primarily in response to the tendency of a defect to repel all others of like kind (charged vacancies are positive relative to normal anion sites and reduced cations are negative with respect to normal cation sites). These repulsive interactions act to divide the assemblages of vacancies and reduced cations into subgroups that represent different energy levels. Each defect in a particular level is, in effect, surrounded by an envelope of sites forbidden to other defects of the same type; the level is then defined by the number of sites in this envelope. The population of each level may be related to its energy, and the energies of the various levels may be interrelated on the assumption that the repulsions are coulombic. The quasi-grand partition function for the defects then contains a series of configurational terms, each representing the distribution of the defects in a particular energy level. The partition function also includes a series of energy terms representing interactions between (a) vacancies and reduced cations, (b) vacancies in the i th and j th levels (for all values of i and j), and (c) reduced cations in the i th and j th levels.

The partition function at equilibrium has been programmed for the CDC 3600 computer, and theoretical curves have been calculated for the relative partial molar thermodynamic quantities as functions of the

⁽³⁶⁸⁾ Rees, A. L. G., *Statistical Mechanics of Two-Component Interstitial Solid Solutions*, Trans. Faraday Soc. **50**, 335-342 (1954).

⁽³⁶⁹⁾ Speiser, R., and Spretnak, J. W., *Thermodynamics of Binary Interstitial Solid Solutions*, Trans. ASM **47**, 493-507 (1955).

45989

FIG. 262. Calculated Relative Partial Molar Entropy and Free Energy of Oxygen in CeO_{2-x} .

defect concentration. Figure 262 illustrates two of these curves for CeO_{2-x} : (a) the entropy ($S_{\text{O}_2}^M$) versus X at 1350°K, and (b) the free energy ($F_{\text{O}_2}^M$) versus X at 910°K (the latter is based on experimental values of $F_{\text{O}_2}^M$) at two points in the CeO_{2-x} phase field). Superimposed on the theoretical curves are points calculated from Bevan and Kordis' experimental data.⁽³⁷⁰⁾

Each of the two slope reversals shown by the free-energy curve is interpreted as the site of a two-phase region. A third two-phase area, indicated by a horizontal or nearly horizontal slope, appears to be developing near $X = 0.06$. The theoretical phase equilibria at 910°K are very similar to the relations intersected by an isothermal section through Bevan and Kordis' proposed phase diagram—the main differences being in the phase boundary compositions.

A detailed description of the statistical model and its application to CeO_{2-x} and UO_{2-x} has been included in a paper submitted to the Journal of the Physics and Chemistry of Solids.

⁽³⁷⁰⁾ Bevan, D. J. M., and Kordis, J., *Mixed Oxides of the Type MO_2 (Fluorite)- M_2O_3 -I*, J. Inorg. Nucl. Chem. **26**, 1509-1523 (1964).

6. Oxygen Diffusion

a. APPLICATION OF PROTON ACTIVATION ANALYSIS (W. K. CHEN AND R. A. JACKSON)

As discussed in the last annual report (ANL-7155), it is desirable to determine oxygen diffusion by direct measurement of O^{18} penetration profiles in solids. The method of locating O^{18} tracers in solids by proton activation has been discussed by Condit and Holt.⁽³⁷¹⁾ By comparison of the diffusion coefficient determined from O^{18} penetration profiles and that from the gaseous isotopic exchange technique, the validity of the assumptions made in the method of gas analysis can be tested.

Such tests have been made on $\alpha\text{-Nb}_2\text{O}_5$ single crystals. This material is suitable for such analysis, because oxygen diffusion is sufficiently rapid and niobium is not subjected to activation by protons at the energy used. Crystals are obtained in the same way as described in the section on page 277. Monocrystal specimens approximately 3 mm x 3 mm x 7 mm were fabricated from polycrystalline boules. After proper heat-treatment, the specimen is heated in the exchange vessel (see Fig. 229, ANL-7155) filled with O^{18} -enriched gas at the required pressure and temperature for a given period of time. The O^{18} -diffused specimen is beveled in the manner of Gatos,⁽³⁷²⁾ along the long dimension at an angle to the original diffusion surface. The beveled surface of the specimen is bombarded with a proton beam of 2.8 Mev for a total of 3×10^8 $\mu\text{a-sec}$. The observed half-life of induced activity is 112 minutes, which agrees well with the published half-life for positron-emitting F^{18} .⁽³⁷³⁾ This verifies that the active centers are a product of the $O^{18}(p,n)F^{18}$ reaction. The distribution of activity along the beveled surface is detected by contact autoradiography. The optical density on the autoradiograph is scanned with a microdensitometer. If the optical density on the photograph is assumed proportional to the radioactivity on the beveled surface, an oxygen penetration profile can be plotted. Figure 263 illustrates a linear plot of $(d - d_i)/(d_0 - d_i)$ versus x , where x is the depth from the original diffusion surface, and d_0 , d and d_i are optical density on the photograph caused by the radioactivity at $x = 0$, $x = x$ and the specimen background, respectively. The sample used for illustration in Figure 263 was heated in 12% O^{18} -enriched oxygen at 170 Torr and 1100°C for 48 hr. The total decrease in O^{18} concentration in the gas phase is about 13% of the original value. As a first approximation, the surface concentration is assumed to be constant

and that there is an instantaneous equilibrium at the gas/solid phase boundary. For these boundary conditions, the concentration of O^{18} , C , at depth x and at time t is given by⁽³⁷⁴⁾

$$\frac{C - C_i}{C_0 - C_i} = \text{erfc} \left(\frac{x}{2\sqrt{DT}} \right) \quad (1)$$

where C_i is the natural abundance of O^{18} (about 0.2%) and D is the diffusion coefficient. The best fit of expression (1) to the experimental points in Figure 263 is obtained when $D = 1.0 \times 10^{-10}$ cm^2/sec . This D value compares reasonably well with $D = 2.04 \times 10^{-10}$ cm^2/sec obtained from gas analysis at the same temperature and oxygen pressure. Therefore, it may be concluded that the boundary conditions assumed for the method of gaseous exchange are reasonable.

b. NEAR-STOICHIOMETRIC $\alpha\text{-Nb}_2\text{O}_5$ (W. K. CHEN AND R. A. JACKSON)

Alpha- Nb_2O_5 is a metal-excess oxide. The metal-excess may arise from presence of either vacant oxygen lattice sites or metal interstitials. Based on the fact that the isothermal electrical conductivity is proportional to $P_{O_2}^{-1/4}$, Greener et al,⁽³⁷⁵⁾ have proposed an oxygen-vacancy model for the near-stoichiometric $\alpha\text{-Nb}_2\text{O}_5$. At high temperatures, the reaction between the oxygen vacancy, the ambient oxygen gas and the conduction electron is expressed by

where O_i , V_0 , e^- , and $\frac{1}{2} O_{2(g)}$ represent, respectively, an oxygen ion at a normal lattice site, a singly ionized oxygen vacancy, a compensating conduction electron, and a half-mole of oxygen in the ambient gas. ΔH_f is the enthalpy for reaction (1).

Application of the law of mass action with the condition of electrical neutrality to the reaction (1), gives the concentrations of oxygen vacancies and the conduction electrons, that is

$$[V_0] = [e^-] = K_1 \exp \left(-\frac{\Delta H_f}{2RT} \right) P_{O_2}^{-1/4}. \quad (2)$$

Since electrical conductivity, σ , is proportional to the concentration of charge carriers, expression (2) gives $\sigma \propto P_{O_2}^{-1/4}$ at constant temperature. However, a metal-excess due to niobium interstitials may also lead to the same oxygen pressure dependence of electrical conductivity when the four outer electrons of the niobium

⁽³⁷¹⁾ Condit, R. H., and Holt, J. F., *J. Electrochem. Soc.* **111**, 1192 (1964).

⁽³⁷²⁾ Gatos, H. C., and Kurtz, A. D., *J. Metals* **6**, 616 (1954).

⁽³⁷³⁾ Hollander, J. M., Perlman, I., and Seaborg, G. T., *Rev. of Modern Physics*, **25**, 480 (1953).

⁽³⁷⁴⁾ Crank, J., *Mathematics of Diffusion*, (Clarendon Press, Oxford, 1956) p. 19.

⁽³⁷⁵⁾ Greener, E. H., Whitmore, D. H., and Fine, M. E., *J. Chem. Phys.* **34**, 1017 (1961).

45935

FIG. 263. O^{18} Penetration Profile in $\alpha\text{-Nb}_2\text{O}_5$ Crystal Heated to 1100°C at $P_{O_2} = 170$ Torr, for $t = 48$ hr. $\odot$, measured as optical density on autoradiograph, and —, calculated with $D = 1.0 \times 10^{-10}$ cm^2/sec .

interstitial are free to migrate. Therefore, it is difficult to distinguish between the two models conclusively by electrical conductivity measurements alone. Therefore, a study of oxygen diffusion in near-stoichiometric $\alpha\text{-Nb}_2\text{O}_5$ as a function of temperature and oxygen pressure has been made to determine which mechanism is operative.

For diffusion measurements, the gas/solid O^{18} exchange method was employed. The method adopted here basically follows that of previous investigators.⁽³⁷⁶⁾ In brief, the metal oxide is heated in a constant and limited volume of O^{18} enriched oxygen gas. From the rate of depletion of O^{18} concentration in the gas phase, the diffusion coefficient in the solid is evaluated. A solution of Fick's equation for the diffusion of solute from a limited and constant volume of well-stirred gas into a spherical solid is given by Crank.⁽³⁷⁷⁾ The assumption of an instantaneous phase-boundary reaction has

⁽³⁷⁶⁾ Among others, see for example, Kingery, W. D., Pappis, J., Doty, M. E., and Hill, D. C., *J. Am. Ceram. Soc.* **42**, 393 (1959).

⁽³⁷⁷⁾ Crank, J., *Mathematics of Diffusion*, (Clarendon Press, Oxford, 1956), p. 88.

45860

FIG. 264. Diffusion Coefficients of Oxygen in $\alpha\text{-Nb}_2\text{O}_5$, as a Function of Temperature at $P_{O_2} = 0.23$ atm., Plotted as $\log D$ vs $1/T$.

been used for analysis in this study. Details of apparatus, experimental procedure and data analysis have been reported elsewhere.^(378,379) Small $\alpha\text{-Nb}_2\text{O}_5$ crystals used for diffusion measurements were obtained from boules grown by the Verneuil process in an arc-image furnace. Particle sizes ranged from 80 to 230 microns in diameter.

Figure 264 gives the observed temperature dependence of the diffusion coefficient at an oxygen pressure of 0.23 atmosphere. The best straight line fitted by the method of least squares is represented by

$$D = 1.72 \times 10^{-2} \exp \left(- \frac{49.4 \pm 3.3 \text{ kcal}}{RT} \right) \text{ cm}^2/\text{sec}. \quad (3)$$

Figure 265 shows a log-log plot of D versus P_{O_2} at a constant temperature of 1100°C . It indicates that, at a constant temperature, the diffusion coefficient of oxygen increases with decreasing oxygen pressure. A straight line, with slope $= -1/4$, fits reasonably well within the uncertainties at each point. Therefore, D

⁽³⁷⁸⁾ Metallurgy Division Annual Report for 1965, ANL-7155, p. 243.

⁽³⁷⁹⁾ Chen, W. K., and Jackson, R. A., *Diffusion of Oxygen in Near-Stoichiometric $\alpha\text{-Nb}_2\text{O}_5$* , submitted to the *J. Chem. Phys* for publication, December 1966.

45862

FIG. 265. Diffusion Coefficient of Oxygen in α -Nb₂O₅ as a Function of Ambient Oxygen Gas Pressure at 1100°C, Plotted as Log D vs log P_{O_2} .

can be taken as proportional to $P_{O_2}^{-1/4}$ at a constant temperature over the experimental range of oxygen pressures. This result, tends to rule out the possibility of Nb interstitials being responsible for the metal-excess disorder. On the other hand, this supports the vacancy-model in which the singly charged oxygen vacancy is the major defect in near-stoichiometric α -Nb₂O₅ and that the oxygen migrates via a vacancy mechanism.

If diffusion of oxygen takes place only by random motion of oxygen vacancies, the diffusion coefficient of oxygen, D , is related to the diffusion coefficient of vacancies, D_v , by ⁽³⁸⁰⁾

$$D = [V_0]D_v \quad (4)$$

Combining (2) and (4), and expressing D_v in the usual pre-exponential and exponential terms, D is expressed by

$$D = D_0 P_{O_2}^{-1/4} \exp \left[- \frac{(\Delta H_f/2 + \Delta H_m)}{RT} \right] \text{cm}^2/\text{sec} \quad (5)$$

where $D_0 = K_1 \cdot D_{v0}$ and ΔH_m is the enthalpy for oxygen vacancy migration. Thus, the experimentally measured enthalpy of activation, ΔH , is given by

$$\Delta H = \frac{1}{2} \Delta H_f + \Delta H_m = 49.4 \pm 3.3 \text{ kcal}$$

From electrical conductivity measurements, the value of 65 to 76 kcal is assigned to ΔH_f by previous investigations.^(375,381) Taking $\Delta H_f \cong 65$ kcal, one obtains $\Delta H_m \cong 20$ kcal. The mole-fraction of oxygen vacancies may be estimated from Equation (4), With $D = 2.04 \times$

⁽³⁸⁰⁾ See for example, Wagner, C., in *Atom Movements* (American Society for Metals, Cleveland, Ohio, 1951) p. 165.

⁽³⁸¹⁾ Chen, W. K., and Swalin, R. A., *J. Phys. Chem. Solids* **17**, 57 (1966).

45936

FIG. 266. Temperature Dependence of the Oxygen Diffusion Coefficient in CoO at $P_{O_2} = 160$ Torr, Plotted as Log D vs $1/T$.

10^{-10} cm²/sec at 1100°C, $P_{O_2} = 0.23$ atm., and $D_v = 1.9 \times 10^{-7}$ cm²/sec (from Ref. 381) at the same temperature, $[V_0] \approx 1 \times 10^{-3}$ is obtained. This value gives the extent of nonstoichiometry for which the diffusion coefficients have been determined.

c. COBALT MONOXIDE (W. K. CHEN AND R. A. JACKSON)

Cobalt monoxide, CoO, is an oxygen-excess *p*-type semiconductor in most of its stable range of composition. Excess oxygen in the lattice may arise from oxygen interstitials or cation vacancies. From considerations of lattice parameter and ionic radii, it is generally accepted that the cation vacancy is the most probable defect in CoO. This is supported by the work of Carter and Richardson,⁽³⁸²⁾ who found that the diffusion coefficient of cobalt in CoO increases with oxygen pressure. The diffusion coefficient of oxygen in CoO has been measured previously by Thompson⁽³⁸³⁾ in the temperature range of 900 to 1000°C and at $P_{O_2} = 100$ Torr. Even though the data are quite scattered, they indicate that oxygen diffusion coefficients are about two to three orders of magnitude lower than the cation diffusion coefficients. This study intends to learn the mechanism of oxygen

⁽³⁸²⁾ Carter, R. E., and Richardson, F. D., *Trans. AIME* **200**, 1244 (1954).

⁽³⁸³⁾ Thompson, B. A., PhD Thesis, Rensselaer Polytechnic Institute, 1962.

diffusion and the nature of defects involved by studying oxygen diffusion in CoO at various degrees of non-stoichiometric disorder. The extent of disorder is controlled by equilibrating CoO at different oxygen pressures and by doping with monovalent and trivalent ions.

The oxygen diffusion coefficients in pure CoO have been measured in the temperature range of 1150 to 1500°C and at $P_{O_2} = 160$ Torr with the gas/solid O^{18} exchange method. The apparatus and procedures are, in general, similar to that described in another section of this report. Cobalt monoxide specimens, in thin slab form, were cleaved from single crystals. A solution for the thin slab geometry, given by Crank,⁽³⁸⁴⁾ was used for computing the diffusion coefficient. For practical

purposes, a computer program (MET-178) was coded to compute the diffusion coefficient graphically.

Figure 266 illustrates the temperature dependence of oxygen diffusion in CoO at $P_{O_2} = 160$ Torr. The diffusion coefficient can be expressed by

$$D = (87 \pm 27) \exp \left(- \frac{97 \pm 10 \text{ kcal}}{RT} \right) \text{ cm}^2/\text{sec.}$$

The activation energy for oxygen diffusion obtained from the present work is 97 kcal, which is much higher than 36 kcal given by Thompson.⁽³⁸³⁾ Since most of Thompson's measurements were done on polycrystalline spheres at low temperatures, diffusion along grain boundaries may be significant. A study on whether or not oxygen diffuses preferentially along grain boundaries is also in progress with proton activation analysis on CoO bicrystals.

⁽³⁸⁴⁾ Crank, J., *Mathematics of Diffusion* (Clarendon Press, Oxford, 1956) (Equa. 4.43), p. 54.

7. Interface Migration in Alkali Halides (C. F. GIBBON)

Publication

C. F. Gibbon, *Grain-Boundary Migration in Potassium Chloride Bicrystals*, ANL-7232 (August 1966).

This program was initiated to study the nature of grain-boundary migration in ionic solids and results of the initial stages are reported in the above publication. The conclusions detailed in the report can be summarized as follows: (1) The technique of using a bicrystal in the shape of a right triangular prism with the grain-boundary parallel to one of the faces, providing a driving-force for migration, was found to be a convenient method for examining boundary migration.

(2) Preliminary measurements indicate no effect of crystallographic misorientation across the boundary on its mobility. (3) Boundary mobility decreases with time, possibly because of accumulation of impurities during migration. (4) The migration activation energy is extremely large, again, an indication of probable impurity segregation.⁽³⁸⁵⁾ (5) A rigid-lattice calculation of twist-boundary energies was also made and suggests that the boundary energy is insensitive to boundary misorientation in this approximation.

⁽³⁸⁵⁾ Cahn, J. W., *Acta Met.*, **10**, 789 (1962).

I. X-RAY AND NEUTRON DIFFRACTION STUDIES

I. Diffraction Instrumentation (M. H. MUELLER, L. HEATON, J. WILLIAMS,* AND H. KNOTT)

a. COMPUTER CONTROLLED DIFFRACTION UNITS

The application of computer control for diffraction instruments is being carried out with the Applied Mathematics Division. To date one IBM-1130 computer has been obtained for the initial development. A number of programs have been adapted from our basic programs or new ones written where necessary for calculation of angles for observation of reflections, least-squares calculation of unit cell constants, collection of intensity data by use of computer registers, motor control for angle positioning as well as a number

45992

FIG. 267. X-ray Beam Shutter for G. E. X-ray Collimator.

of smaller programs such as: single-reflection data collection, peak seeking and position refinement, monitor intensity periodic sampling, etc. These programs are stored on the 500K disc of this computer and are readily accessible to the 4K storage, which has considerable advantage over a system of paper tape input. A large part of the 500K disc storage will be available for data collection. It has been determined to drive all instrument shafts with Slo-Syn stepping motors coupled with Gurley optical angle encoders. Presently as many as six motors may be driven simultaneously with computer control. The basic delay in attaching this com-

puter to our Neutron Diffractometer at CP-5 has been the delay by IBM in furnishing the input channel as an auxiliary device. This is now promised for delivery by early February. A second 1130 computer has been ordered by the Metallurgy Division for installation on a second Neutron Diffractometer, and several additional ones are on order by other divisions for use on X-ray or neutron instruments.

b. AUXILIARY EQUIPMENT

The Cryo-Orienter briefly described in the last Annual Report⁽³⁸⁶⁾ has been constructed except for one Messinger bearing whose installation has been delayed repeatedly because of fabrication difficulties. This instrument will permit the orientation of a crystal with $\pm 0.01^\circ$ precision about two axes—the phi and chi motions of the orienter—while the crystal is held at constant temperatures in the range from liquid He to room temperature. This capability will permit collection of 3D neutron-diffraction data. Delivery of the bearing, which has been definitely promised by early January, should make it possible to complete the assembly and installation of this instrument on the Neutron Spectrometer. The cryostat, capable of rotation and tilt to 55° from vertical, has been modified and returned by Hofman after our initial rejection. Sample temperature uniformity will be assured by exchange gas surrounding the sample. Temperature control will be achieved by a bridge circuit with temperature sensing with germanium at the lower temperatures and a platinum resistance thermometer above 20°K .

An electromagnet that will provide a 20°K gauss field about a sample has been purchased for use on Neutron Spectrometer II. The magnet has coils of copper foil tapered to allow a 60° cone access for the neutron beam into the magnet pole region. The magnet is supported on bearings permitting a horizontal rotation of the entire magnet with a 110° minimum motion. This provides for both horizontal and vertical field application.

Several auxiliary devices have been designed and constructed for the G. E. X-ray Diffractometer. A push-rod collimator beam stop has been designed for use with the crystal orienter in place of the hinged flip-flop beam stop, which is unstable and inconvenient to operate. The present unit (Figure 267) makes use of

* Resident Research Associate from Washington State University, Pullman, Washington.

⁽³⁸⁶⁾ Annual Report for 1965, Metallurgy Division, ANL-7155, p. 248.

a ball-point top mechanism in which a small rod with a lead or brass plug takes the place of the usual ink cartridge. This entire mechanism is then mounted in a drill and tapped hole in the top side of the collimator. The X-ray beam is then cut on and off by depressing the usual ball-point pen tip. This design has the further advantage that the ball-point mechanism can be easily replaced with a solenoid for remote and/or automatic operation.

A Ross filter holder has also been constructed for use in the diffracted beam on the G. E. Diffractometer. It consists of an aluminum disc 2.5 in. O.D. and 0.625 in. thick. This disc may be rotated to positive fixed posi-

tions 45° apart by means of a rotary solenoid. This provides a means of alternately positioning the required two filter foils accurately in the diffracted beam for intensity measurement. Since the disc is thick the foils are mounted across the diameter of small cylinders inserted along radii of the disc. By rotation of these small cylinders it is possible to adjust the effective thickness of the filter foils and thus attain a balance of intensity. This project was prompted especially by our need to carefully measure the X-ray diffracted intensities from α -uranium as well as a means for obtaining rapid intensity measurements for structure analyses.

2. Design of Neutron Instruments for AARR (R. BLESCH AND L. HEATON)

The AARR Neutron Diffraction Equipment Design Committee is in the early stages of designing a group of diffractometers. It is an interdivisional effort involving Applied Mathematics, Chemistry, Electronics, Metallurgy, and Solid State Science. The Committee is following the direction set forth in "Recommended Neutron Diffraction Instruments and Operating Policy for AARR," dated 2 May 1966. In a broad sense, the purpose of the Design Committee is to coordinate the neutron diffraction needs of the Laboratory so that a group of instruments is available at AARR that makes maximum use of the high flux at AARR and satisfies the requirements of both Laboratory and University research in future years. The Committee is now establishing design criteria and proceeding with pre-

liminary design. To this end, the latest equipment at other laboratories is being inspected and studied in some detail; the designers and users are being consulted. A serious attempt is being made to fully utilize the latest technology in computer control, data handling, instrumentation, etc. As a step towards developing a computer control system that is compatible with the requirements of all the divisions, an IBM-1131 computer system is being mated to some of the neutron diffraction equipment currently being used at CP-5. It is hoped that this same approach to other areas, such as detectors, will allow a full compliment of instruments to be put into operation as soon as AARR is completed.

3. Crystallographic Computer Programs

a. SECONDARY EXTINCTION CORRECTION PROGRAM B-260 (JACK M. WILLIAMS* AND J. GVILDYS**)

When an X-ray or neutron beam is incident upon a crystal, and the Bragg condition for diffraction by any set of planes is satisfied, there is an attenuation of the primary beam intensity known as *secondary* "extinction." The diffraction process itself diverts energy from the primary beam thereby weakening it. This behavior is similar to ordinary absorption and has generally

been treated as additive to the linear absorption coefficient.

A first-order secondary "extinction" correction⁽³⁸⁷⁾ may be applied directly to the "structure factor" (F_{hkl}) derived from Bragg intensity measurements through use of the following relationship

$$F_{\text{corr}} \approx KF_{\text{obs}} [1 + \beta CI_{\text{obs}}],$$

where

F_{corr} = "structure factor" corrected for secondary extinction,

* Resident Research Associate from Washington State University, Pullman, Washington.

** Applied Mathematics Division, ANL.

⁽³⁸⁷⁾ Zachariasen, W. H., *The Secondary Extinction Correction*, Acta Cryst. **16**, 1139-1144 (1963).

K = a scaling factor,

β = unity for neutron diffraction but a function of 2θ for the X-ray case,

C = a constant derived from a plot of $[(F_{\text{calc}}/F_{\text{obs}}) - 1]$ vs I_{obs} ,

and

I_{obs} = a measured integrated intensity.

Program B-260 consists of two parts. In the first portion the constant C is derived after a least-squares line has been calculated for the above mentioned plot. The second portion provides a CALCOMP plot of $[(F_{\text{calc}}/F_{\text{obs}}) - 1]$ vs I_{obs} with the least-squares line inserted. Various options are provided and certain intensity limits may be selected for least-squares analysis. The output is listed and optional punched cards may be used as direct input to MET-153 for crystal structure refinement by the least-squares process.

Program B-260 has been used successfully for secondary extinction corrections to neutron diffraction data obtained for selenious acid where final least-squares refinement was possible only after the making of such corrections.

b. SINGLE-CRYSTAL ABSORPTION CORRECTION PROGRAM MET-176X (JACK M. WILLIAMS*)

Structure factors derived from integrated intensity measurements in neutron or X-ray diffraction usually require a correction for absorption of radiation in the specimen. Tabulated values of this correction, expressed as the ratio of integrated intensity yielded by an absorbing specimen to that yielded by a hypothetical nonabsorbing specimen of equal volume, are available in the literature for cylindrical and spherical sample shapes. For accurate measurement of structure factors, the specimen is often reduced to one of these simple forms if possible. However, it frequently proves undesirable or difficult to shape a sample. An absorption correction calculation on a sample of arbitrary shape is

* Resident Research Associate from Washington State University, Pullman, Washington.

then required. This program allows calculation of the absorption correction factor for each reflection from a crystal of essentially arbitrary shape.

Program MET-176X is an adaptation of an existing program⁽³⁸⁸⁾ for the ANL CDC-3600 computer. The program has been expanded to handle crystals with up to 100 boundaries (plane faces). An absorption correction is calculated for each (hkl) and use of this version of the program can yield an estimated precision in the absorption correction of $\pm 0.2\%$ with a maximum deviation of 0.5% .

The present program speed is approximately 170 reflections per minute.

c. PHASE DETERMINATION BY SOLUTION OF A TRIPLE-PRODUCT RELATIONSHIP B-256 (N. KENT DALLEY* AND J. GVILDYS**)

With the increased use of high-speed computers new more complicated relationships can be used for phase determination in centrosymmetric crystals with equal atoms. Such a relationship is

$$E_{h_1}E_{h_2}E_{h_3} \cong \frac{N^{3/2}}{8} \langle (E_k^2 - 1)(E_{h_1+k}^2 - 1) \\ (E_{h_1+h_2+k}^2 - 1) \rangle_k + \frac{1}{N^{1/2}} (E_{h_1}^2 + E_{h_2}^2 + E_{h_3}^2 - 2)$$

where $h_1 + h_2 + h_3 = 0$.

This relationship allows the use of more data in determining signs than do the more simple Σ_1 , Σ_2 and Σ_3 formulas. It has been proposed⁽³⁸⁹⁾ that this relationship has value in obtaining signs in the initial stages of phase-determining procedures. Three-dimensional data are required. A FORTRAN program has been written for this relationship for crystals of monoclinic and higher symmetry.

⁽³⁸⁸⁾ Wehe, D. J., Busing, W. R., and Levy, H. A., *ORABS, A FORTRAN Program for Calculating Single Crystal Absorption Corrections*, ORNL-TM-229, April (1962).

* Resident Student Associate from University of Texas, Austin, Texas.

** Applied Mathematics Division, ANL.

⁽³⁸⁹⁾ J. S. Rollett, ed., *Computing Methods in Crystallography*, Pergamon Press, Oxford, 1965, p. 163-165.

4. Thermal Neutron Scattering Amplitudes of Ni⁶¹ and Ni⁶⁴ (S. S. SIDHU AND K. D. ANDERSON)

The element nickel contains five stable isotopes of mass numbers 58, 60, 61, 62 and 64 with isotopic abundances of 67.88, 26.23, 1.19, 3.66 and 1.08 atomic percent respectively. The coherent nuclear scattering

amplitudes for 58, 60 and 62 are known; the isotope 62 possessing an anomalous negative scattering amplitude. Since isotopes of 61 and 64 mass became available in sufficient amount it was of interest to determine

TABLE 95. ISOTOPIC PURITY OF NICKEL 61 AND 64 SAMPLES

Isotope	Ni ⁶¹ Atomic Percent	Ni ⁶⁴ Atomic Percent
Ni ⁵⁸	1.62 ± 0.05	0.85 ± 0.05
Ni ⁶⁰	5.18 ± 0.05	0.56 ± 0.05
Ni ⁶¹	92.11 ± 0.1	0.05
Ni ⁶²	1.08 ± 0.05	0.39 ± 0.05
Ni ⁶⁴	<0.05	98.15 ± 0.1

rections were also made for the isotopic impurities in this sample. The resulting thermal neutron scattering amplitude is $0.760 \pm 0.006 \times 10^{-12}$ cm.

Ni⁶⁴: Neutron diffraction patterns of nickel (64) showed that it was an extremely poor scatterer of thermal neutrons. The weak diffraction peaks observed at room temperature were mostly magnetic as confirmed by their practical disappearance in the pat-

TABLE 96. RESULTS OF GRAPHICAL AND LEAST-SQUARES REFINEMENT OF SCATTERING AMPLITUDES

Isotopic Sample	Form	No. of Lines Used	b_{Ni^x} (10^{-12} cm)				Isotopic b (10^{-12} cm)
			Graphical	L.S. refinement	Mean ^(a)	Correction for isotopic impurities	
Ni ⁶¹	Metal	9	0.725	0.725 ± 0.005	0.730 ± 0.005	+0.0295 ± 0.0012 ^(b)	0.760 ± 0.006
Ni ⁶¹	Oxide	8	0.735	0.735 ± 0.005			
Ni ⁶⁴	Oxide	13	-0.017 -0.035	-0.027 ± 0.002	-0.026 ± 0.007	-0.0110 ± 0.0002	-0.038 ± 0.007

^(a) Mean of the graphical values from plots and computer least-squares treatment.

^(b) For this calculation a standard error of ± 0.02 was assumed for the b of Ni⁵⁸, Ni⁶⁰, and Ni⁶² which are the primary impurities and ± 0.007 for Ni⁶⁴.

their scattering values. It was recognized that corrections had to be applied because of isotopic impurities as shown in Table 95.

X-ray and neutron diffraction patterns were made of these samples both in the metallic form and in the oxide form. Nickel oxide was prepared by dissolving each sample in nitric acid, evaporating to dryness, and igniting at 1000°C. Since the neutron patterns of the oxide samples, taken at room temperature, contained antiferromagnetic peaks the final patterns were made at 300°C, which is above the Néel temperature of 250°C for NiO.

Ni⁶¹: The integrated intensities of diffraction peaks obtained from a neutron pattern of the nickel (61) sample and its oxide were put on an absolute basis by the usual method described previously.⁽³⁹⁰⁾ The structure factors, $|F_{hkl}|$, for the reflections from the metal and oxide were analyzed with graphical and least-squares refinements as summarized in Table 95. Cor-

tern taken at 365°C, which is above the Curie temperature of nickel. Hence, it was not possible to determine the coherent nuclear scattering amplitude from this sample, however, an atomic magnetic moment of nickel of $0.60 \mu_B$ was obtained from these peaks.

The integrated intensities from the diffraction pattern of nickel (64) oxide were put on an absolute basis. These were then treated graphically and with a least-square refinement as summarized in Table 96. After corrections were made for the isotopic impurities a b value of $-0.038 \pm 0.007 \times 10^{-12}$ cm was obtained for the Ni⁶⁴ isotope. This is the first instance where a second isotope of the same element has been found to possess an anomalous negative scattering amplitude. A more complete description of this investigation has been accepted for publication in Physical Review.

⁽³⁹⁰⁾ Sidhu, S. S., Heaton, L., and Mueller, M. H., J. Appl. Phys. **30**, 1323-1340 (1959).

5. Structure Determination of Manganese Silicide (H. KNOTT, M. H. MUELLER, AND L. HEATON)

The crystal structure of Mn₁₅Si₂₆ has been determined by X-ray diffraction. In the previous annual report,⁽³⁹¹⁾ this phase was reported as an Mn₄Si₇ compound; and the report structure was based on 1700 sin-

⁽³⁹¹⁾ Annual Report for 1965, Metallurgy Division, ANL-7155, p. 252.

gle crystal reflections, which gave a final R factor of 7.5%. Since that time the phase has been reported elsewhere⁽³⁹²⁾ as Mn₁₁Si₁₉ with limited information obtained from zone data. On examination of a different

⁽³⁹²⁾ Schwomma, O., Preisinger, A., Nowotny, H., and Wittman, A., Monatshefte Fur Chemie **95**, 1527 (1964).

TABLE 97. COMPARISON OF DATA FOR VARIOUS MNSI CELLS

Space Group	Mn ₄ Si ₇			Mn ₁₁ Si ₁₉			Mn ₁₅ Si ₂₈		
	$P4c2$			$P4n2$			$I42d$		
Chromium Radiation Powder Pattern-28 Reflections	$a_0(\text{\AA})$ 5.5337(30)	$c_0(\text{\AA})$ 17.5504(96)	$\Sigma v^2/(N-K-1)\Sigma w$ 3.78×10^{-7}	$a_0(\text{\AA})$ 5.5295(21)	$c_0(\text{\AA})$ 47.7627(185)	$\Sigma v^2/(N-K-1)\Sigma w$ 1.94×10^{-7}	$a_0(\text{\AA})$ 5.5307(12)	$c_0(\text{\AA})$ 65.3107(145)	$\Sigma v^2/(N-K-1)\Sigma w$ 6.34×10^{-8}
Molybdenum Radiation Single Crystal (00l) Scan-14 Reflections	$\Sigma d_{\text{obs}} - d_{\text{cal}} (\text{\AA})$ 0.6780	Ave $\Delta d (\text{\AA})$ 0.0484		$\Sigma d_{\text{obs}} - d_{\text{cal}} (\text{\AA})$ 0.2002	Ave $\Delta d (\text{\AA})$ 0.0143		$\Sigma d_{\text{obs}} - d_{\text{cal}} (\text{\AA})$ 0.0579	Ave $\Delta d (\text{\AA})$ 0.0041	
Molybdenum Radiation Single Crystal-18 Reflections	$\Sigma \chi_{\text{obs}} - \chi_{\text{cal}} (^{\circ})$ 4.47	Ave $\Delta \chi (^{\circ})$ 0.25		$\Sigma \chi_{\text{obs}} - \chi_{\text{cal}} (^{\circ})$ 1.74	Ave $\Delta \chi (^{\circ})$ 0.10		$\Sigma \chi_{\text{obs}} - \chi_{\text{cal}} (^{\circ})$ 0.58	Ave $\Delta \chi (^{\circ})$ 0.03	
Copper Radiation Single Crystal Rotation Pattern Around c-Axis	No. l layers	$\Sigma \Delta l $	Ave Δl	No. l layers	$\Sigma \Delta l $	Ave Δl	No. l layers	$\Sigma \Delta l $	Ave Δl
	6	1.990	0.332	6	1.846	0.308	6	0.204	0.034
	7	1.792	0.256	7	1.357	0.194	7	0.749	0.107
	6	1.953	0.326	6	2.026	0.338	6	0.185	0.031

single crystal and observation of about 4000 reflections, we have determined that the phase is $\text{Mn}_{15}\text{Si}_{26}$; and the R factor for the space group assigned is 4.4%.

There are two reasons for accurately determining the correct formula and space group. First, MnSi_2 has for thirty years been considered a type structure, when in fact the formula is near $\text{MnSi}_{1.7}$. The cell has long been reported as a tetragonal with a_0 near $5.5\text{\AA}$ and c_0 near $16\text{\AA}$, but recent investigations have reported c_0 's near $17\text{\AA}$,⁽³⁹³⁾ $48\text{\AA}$,⁽³⁹⁴⁾ $65\text{\AA}$,⁽³⁹⁵⁾ and $112\text{\AA}$,⁽³⁹⁵⁾ depending upon the exact composition. These are all unusually long cells.

Second, many similar compounds exist in the range $\text{AB}_{1.3}$ to AB_2 , where A is a metal of Group 5B, 6B, 7B, or 8; and B is a nonmetallic element of Group 4A. They are not necessarily isostructural compounds, but all are similar in being tetragonal cells with a_0 around $6\text{\AA}$ and very long c_0 's. Determination of the atomic ar-

angement in $\text{Mn}_{15}\text{Si}_{26}$ may aid in the understanding of many similar compounds.

Table 97 shows quantitative comparisons for three variously sized manganese silicide cells that we have considered. Each method of measurement was indexed for three cells with different c_0 lengths in order to determine the best agreement of observed data with calculated cell size. First, powder patterns were indexed to determine lattice constants, probable errors, and the standard deviations of the $\sin^2 \theta$'s. Second, the deviations between observed d -spacings and those calculated for the three cells were totaled for all $(00l)$ reflections. Third, the difference between observed and calculated chi readings on the instrument used were noted. The sample was oriented such that a change in chi represented only a change in l index, hence a change in c_0 of the unit cell. Last, the deviation from integral values of l was measured on three rotation patterns.

All of this information together with our solution of the structure by use of several computer programs to a refinement of the previously mentioned 4.4% agreement indicate that $\text{Mn}_{15}\text{Si}_{26}$ is the true formula. The complete structure is described in a paper accepted for publication in *Acta Crystallographica*.

6. Neutron Diffraction Study of Uranyl Nitrate Dihydrate

(N. K. DALLEY,* M. H. MUELLER, AND
S. H. SIMONSEN**)

The crystal structure of uranyl nitrate dihydrate has been determined by neutron diffraction. Such a study is of importance since it is a continuation of our previous investigations^(396,397) of (1) the coordination of the metal atoms and (2) hydrogen bonding in inorganic structures. An X-ray study of this same material was reported earlier by Vdovenko et al.⁽³⁹⁸⁾ but this study was limited in that positional parameters were taken directly from two-dimensional Patterson and Fourier maps and no refinement was attempted. Also the X-ray study was unable to locate the positions of the light scattering hydrogens in the presence of the heavy scattering and highly absorbing uranium atoms.

* Resident Student Associate from University of Texas, Austin, Texas.

** Faculty Associate from University of Texas, Austin, Texas.

⁽³⁹⁶⁾ Taylor, J. C., Mueller, M. H., and Hitterman, R. L., *Acta Cryst.* **20**, 842 (1965).

⁽³⁹⁷⁾ Taylor, J. C., and Mueller, M. H., *Acta Cryst.* **19**, 536 (1965).

⁽³⁹⁸⁾ Vdovenko, V. M., Stroganov, E. V., Sokolov, A. P., and Lungu, G. L., *Radiokhimiya* **4**, No. 1, 59 (1962).

In the present study the crystal systems of $\text{UO}_2(\text{NO}_3)_2 \cdot 2\text{H}_2\text{O}$ was found to be monoclinic with $a = 14.13$, $b = 8.46$, $c = 7.05\text{\AA}$, $\beta = 107.84^\circ$ and space group $\text{P}2_1/\text{c}$ with four molecules per unit cell. These results differ from the X-ray study which reported space group Cm , $a = 10.52$, $b = 5.93$, $c = 6.95\text{\AA}$, $\beta = 72^\circ$ with two molecules per unit cell. At the present time no correlations can be made between the two studies.

Two thousand three hundred and twenty-one independent reflections were measured on the automated neutron diffractometer. The structure was solved by Patterson and Fourier techniques. After absorption corrections were made a least-squares refinement accounting for anisotropic temperature factors resulted in a weighted R factor of 4.8%. At this point a difference map was run and it was featureless.

The uranyl coordination of the dihydrate, as shown in Figure 268, is similar to that of uranyl nitrate hexahydrate⁽³⁹⁷⁾ and its bond lengths and angles are in good agreement with the hexahydrate study. The four uranium atoms per unit cell occupy special positions

45939

FIG. 268. Configuration about the Uranium Atom of Molecules A and B Found in $\text{UO}_2(\text{NO}_3)_2 \cdot 2\text{H}_2\text{O}$.TABLE 98. HYDROGEN BOND DISTANCES AND ANGLES FOUND IN $\text{UO}_2(\text{NO}_3)_2 \cdot 2\text{H}_2\text{O}$

Hydrogen Bond	O—O Length	O—H—O Angle
O(3)—H(31)—O(12)	2.83 Å	165.4°
O(3)—H(32)—O(2)	2.97 Å	145.7°

(a) and (b) of the space group, $P2_1/c$. Each uranyl group is surrounded by a near perpendicular planar oxygen hexagon. This hexagon consists of two oxygens from each of two equivalent bidentate nitrate groups and two oxygens from equivalent water molecules. The near planar coordination group about the uranium at position (a) (Molecule A) is nearly perpendicular to the b axis while the coordination about the uranium on a (b) site (Molecule B) is almost parallel to the b axis. The molecules are linked together by hydrogen

bonds. There is a fairly strong hydrogen bond (see Table 98) joining the water oxygen of a molecule B to an uncoordinated nitrate oxygen of a molecule A. A weaker hydrogen bond joins the water oxygen of a molecule B to a uranyl oxygen of another molecule B. The structure can be thought of as long chains of alternating A and B molecules joined to each other by rather strong hydrogen bonds. Each link consists of a uranium atom and its planar coordinated hexagon as shown in Figure 268. Each joining link is then perpendicular to its neighbor. These chains are connected by a cross linkage of very weak hydrogen bonds between B molecules.

This is considerably different hydrogen bonding scheme than that found in the hexahydrate where the uranyl coordination groups are joined together by means of hydrogen bonded planar water sheets.

7. Crystal Structure of Selenious Acid (JACK M. WILLIAMS,* R. L. HITTERMAN, AND M. H. MUELLER)

Selenious acid, H_2SeO_3 , is a dibasic inorganic acid that has been studied by nuclear magnetic resonance,⁽³⁹⁹⁾ infrared^(400,401) and Raman⁽⁴⁰²⁾ spectroscopy,

* Resident Research Associate from Washington State University, Pullman, Washington.

⁽³⁹⁹⁾ Birchall, T., Gillespie, R. J., and Verkris, S. L., *Nuclear Magnetic Resonance Spectroscopy of Some Selenium Compounds*, Can. J. Chem. **43**, 1672 (1965).

⁽⁴⁰⁰⁾ Detoni, S., and Hadzi, D., *Les Spectres Infrarouges Des Acides Benzene-Et Toluene-Seleniniques Et De L'Acide Selenieux*, J. Chim. Phys. **53**, 760 (1956).

⁽⁴⁰¹⁾ Falk, M., and Giguere, P. A., *Infrared Spectra and Structure of Selenious Acid*, Can. J. Chem. **36**, 1680 (1958).

⁽⁴⁰²⁾ Simon, A., and Paetzold, R., *The Raman Spectrum of Solid Selenious Acid*, Naturwissenschaften **44**, 108 (1957).

copy, and X-ray diffraction.⁽⁴⁰³⁾ A neutron diffraction investigation was undertaken since (1) both infrared and X-ray diffraction studies have indicated the presence of "strong" hydrogen bonds. However the infrared O—H stretching frequencies were not⁽⁴⁰¹⁾ in agreement with those derived from approximate correlation diagrams⁽⁴⁰⁴⁾ of O—O distance vs O—H stretching frequency. The X-ray study⁽⁴⁰³⁾ had yielded O—O dis-

⁽⁴⁰³⁾ Wells, H. G., and Bailey, M. J., *The Structures of Inorganic Oxy-Acids, The Crystal Structure of Selenious Acid*, J. Chem. Soc. 1282 (1949).

⁽⁴⁰⁴⁾ Rundle, R. E., and Parasol, M., *O—H Stretching Frequencies in Very Short and Possibly Symmetrical Hydrogen Bonds*, J. Chem. Phys. **20**, 1487 (1952).

tances of 2.56 and 2.60 Å; (2) From infrared studies⁽⁴⁰¹⁾ Falk and Giguere had suggested the presence of "bent" hydrogen bonds in the acid; (3) The three Se—O distances reported in the X-ray study were not consistent with those found⁽⁴⁰⁵⁾ in $\text{NaH}_3(\text{SeO}_3)_2$, and $\text{LiH}_3(\text{SeO}_3)_2$; (4) If, as indicated in the X-ray study, there existed a hydrogen bond as short as 2.56 Å in H_2SeO_3 , the compound might be ferroelectric for the same reason as $\text{LiH}_3(\text{SeO}_3)_2$. In $\text{LiH}_3(\text{SeO}_3)_2$ ferroelectricity arises because of a double well potential function for two of the three hydrogen atoms with subsequent "disorder" in their atom positions.⁽⁴⁰⁶⁾ This "disorder" produces "half-hydrogen" atoms in the Fourier syntheses of the neutron scattering density from the crystal; (5) In the X-ray diffraction study,⁽⁴⁰³⁾ in which only partial-zonal data were used, none of the hydrogen atoms was located and one oxygen atom coordinate could only be inferred because of extensive Se—O overlap in the projection used.

The present investigation confirmed that the acid is orthorhombic, space group $\text{P2}_12_12_1$, with $a = 9.138 \pm 0.013 \text{ Å}$, $b = 5.984 \pm 0.008 \text{ Å}$, and $c = 5.085 \pm 0.007 \text{ Å}$. The unit cell contains four molecules. A total of 362 independent reflections were collected and the structure solved by Fourier techniques. A full-matrix least-squares refinement yielded a final weighted discrepancy factor $wR = 7.5\%$.

The structure is similar to that reported in the X-ray study but the bond distances are quite different with the hydrogen bonding being quantitatively much different. The hydrogen bonds (indicated by dashed lines in Figure 269) serve to bind the structure together and are definitely of the *hydroxyl* type and are not in crystallographic "disorder." If "disorder" were present the hydrogen atoms would either be apparently "centered" between the oxygen atoms or

⁽⁴⁰⁵⁾ Vedam, K., Okaya, Y., and Pepinsky, R., *Crystal Structure of Ferroelectric $\text{LiH}_3(\text{SeO}_3)_2$* , Phys. Rev. **119**, 1252 (1960).

⁽⁴⁰⁶⁾ Vanden Hende, J. H., and Boutin, H. P., *The Ferroelectric Behavior of $\text{LiN}_3\text{H}_5\text{SO}_4$ and $\text{LiH}_3(\text{SeO}_3)_2$* , Abstracts of the Communications-Sixth International Union of Crystallography, Rome, Italy, p. A193, September 9–18 (1963).

45990

FIG. 269. Projection of Selenious Acid Structure along the b Axis Showing Se—O and Hydrogen Bond Distances.

visible as "half-hydrogen" atoms located symmetrically about the center position between the oxygen atoms of the $\text{O—H} \cdots \text{O}$ bonds.

The acid consists of pyramidal $[\text{SeO}_3]^{-2}$ ions bound together by hydrogen bonds forming chains of H_2SeO_3 molecules extending perpendicular to the $[100]$ direction. The (100) plane is a cleavage plane and this arises because of weak cohesive forces *between* the double layers of H_2SeO_3 molecules bound together by moderately strong hydrogen bonding. As indicated in Figure 269 the Se—O distances (1.65, 1.74, and 1.75 Å) are quite different from those reported in the X-ray study (1.72, 1.75, and 1.76 Å) but almost identical to those reported in $\text{NaH}_3(\text{SeO}_3)_2$ and $\text{LiH}_3(\text{SeO}_3)_2$. The O—H distances (0.93 ± 0.02 and $1.00 \pm 0.01 \text{ Å}$), which were corrected for thermal motion, are clearly of the *hydroxyl* type.

Although neutron diffraction cannot establish the existence of ferroelectricity in a crystal, it is probable that H_2SeO_3 is not ferroelectric because of the lack of disorder in the hydrogen atom positions (assuming ferroelectricity would arise from "disorder" as in lithium and sodium tri-hydrogen selenite).

8. Crystal Structure of Thorium Nitrate Pentahydrate (M. H. MUELLER)

Publication

J. C. Taylor,* M. H. Mueller, and R. L. Hitterman, *Crystal Structure of Thorium Nitrate Pentahydrate by Neutron Diffraction*, Acta Cryst. **20**, 842–851 (1966).

* Present address: AAEC Research Establishment, Sutherland, N.S.W., Australia.

The above article contains a rather complete description of our investigation. As indicated⁽⁴⁰⁷⁾ the simultaneous X-ray investigation⁽⁴⁰⁸⁾ made possible a di-

⁽⁴⁰⁷⁾ Annual Report for 1965, Metallurgy Division, ANL-7155, p. 251.

⁽⁴⁰⁸⁾ Ueki, T., Zalkin, A., and Templeton, D. H., Acta Cryst. **20**, 836 (1966).

rect comparison of the neutron and X-ray results where a heavy atom dominated the X-ray data. Of the 31 independent atom coordinates necessary to describe the positions of all the atoms except the hydrogen atoms, 15, as determined by X-ray, were within one standard deviation and none was as much as three standard deviations from the corresponding neutron results. Another way of describing these differences is to state that these atom positions differed by $0.026\text{\AA}$ on the average and by $0.045\text{\AA}$ in extreme cases. As might be expected the neutron results showed the hydrogen locations were in error by 0.2 to $0.5\text{\AA}$.

The X-ray investigators pointed out that their agree-

ment for the nonhydrogen atoms was even poorer than indicated above before applying the anomalous dispersion correction. It was pointed out that in a polar space group determined from only a set of independent reflections an error in position may be larger than indicated by the standard deviations and not be evident in judging the agreement of F_o and F_c . In comparing neutron and X-ray results an error in the z coordinate for the thorium atom of $0.05\text{\AA}$ was found in the X-ray result. It was estimated that the error in z would have been reduced to zero if the anomalous dispersion correction, $\Delta f''$, had been taken as 10 rather than 9 electrons.

9. Neutron Diffraction Study of Potassium Ferrocyanide Trideuterate (KFCT)

(M. H. MUELLER, J. C. TAYLOR,* AND R. L. HITTERMAN)

In the last Annual Report⁽⁴⁰⁹⁾ the results from the partial neutron diffraction data obtained at room temperature for $\text{K}_4\text{Fe}(\text{CN})_6 \cdot 3\text{D}_2\text{O}$ (KFCT) indicated the positions of the ferrocyanide groups and potassium. There was also some indication of disordered water; however, the Fourier peaks for the deuteriums were

sional Patterson maps were obtained on the complete data to confirm the K, Fe, C, and N starting coordinates. Water positions were located primarily by Fourier difference maps and refinement of positional parameters proceeded with least-squares methods. This later method was unique for this crystal since more than half of the reflections were superimposed; that is, $I_{obs}(hkl) = I_{hkl}(A) + I_{\bar{h}\bar{k}\bar{l}}(B)$ for hkl 's that were eee or ooo , where A and B were the two twinned parts as

46045

FIG. 270. Disordered D_2O Molecule about a Twofold Axis as Found in KFCT.

rather poorly defined. Since that time additional data were obtained so that a total of 2481 reflections were available and corrected for absorption. Three-dimen-

* Present address: AAE Research Establishment, Sutherland, N.S.W., Australia.

⁽⁴⁰⁹⁾ Annual Report for 1965, Metallurgy Division, ANL-7155, p. 252.

46044

FIG. 271. Disordered D_2O Molecules Found in KFCT at $y = \frac{1}{2}$. Numbers in parentheses are distances along the b axis.

indicated previously,⁽⁴⁰⁹⁾ *e* and *o* denote even and odd, respectively. This least-squares method, modified to handle overlapped data, has resulted in an *R* of 5.6% on *F*², a considerable improvement over the 21.5% reported a year ago.

This crystal was investigated with neutrons in order to locate the waters and to detect if disorder exists at room temperature. The present study at R. T. indeed shows two kinds of waters which are disordered as shown in Figure 270 and Figure 271. The water molecule involving O(1) is disordered about the twofold axis and D(1) forms a hydrogen bond of length 2.84Å and D(2) seems attracted to O(2) with a bond length of 2.89Å. The hydrogen bonding about O(2) can be seen at the *y* = ½ layer shown in Figure 271. This water apparently can be described in approximately two alternating positions related by more than a 90°

rotation of the deuteriums about the oxygen. D(3) is at a distance of 3.15 and 3.27Å from N(1) and N(4); D(4) is 3.38Å from N(1) and D(5) forms a hydrogen bond to O(1) at a distance of 2.89Å and is located 3.28Å from N(3). A study of the overlap of the deuteriums from the two waters indicates that the deuteriums of the waters are certainly in dynamic disorder. The basic model proposed by Kiriyaama et al.⁽⁴¹⁰⁾ as a result of an X-ray investigation now seems to agree with the present neutron study. Tsang and O'Reilly⁽⁴¹¹⁾ are endeavoring to interpret their deutron magnetic resonance data in the light of our findings.

⁽⁴¹⁰⁾ Kiriyaama, R., Kiriyaama, H., Wade, T., Niizeki, N., and Hirabayashi, H., *J. Phys. Soc. Japan* **19**, 540-549 (1964).

⁽⁴¹¹⁾ Tsang, T., and O'Reilly, D. E., *J. Chem. Phys.* **43**, 4234 (1965).

10. Structure and Correlation in Liquid Alloys (LeROY HEATON, R. C. BUSCHERT,* AND E. H. HENNIGER*)

Publications

E. H. Henninger, R. C. Buschert, and LeRoy Heaton, *Atomic Structure and Correlation in Liquid Binaries by X-ray and Neutron Diffraction with Application to NaK*, *J. Chem. Phys.* **44**, 1758-1764 (1966).

E. H. Henninger, R. C. Buschert, and LeRoy Heaton, *Structure and Correlation in Liquid Alloys by X-ray and Neutron Diffraction*, Proceedings of Conference on Properties of Liquid Metals, BNL, Upton, New York, September 19-23 (1966) Abstract.

A method for obtaining information about correlation in a liquid alloy has been developed. While the explicit structure in a binary can in principle be determined from three independent diffraction patterns, it is possible to measure and analyze the X-ray and neutron intensity patterns and with these alone obtain considerable correlation information by calculating the ratio of the two experimental radial distributions. For the binary the relevance of the ratio derives from the fact that each distribution is a sum of the radial distributions of the three types of atom pairs, each term being weighted by the appropriate product of scattering amplitudes. The structure of the sample can be analyzed by comparing the ratio for any interatomic

distance to the values it would have for pure A-A, pure B-B, pure A-B and random pairing. In a true liquid the results are semi-quantitative. In an alloy with well-defined short range order, the correlation of these close pairings can be clearly determined. This method applied to an equiatomic NaK alloy shows concentration of NaK pairs at 4.4, 7.7 and 11.2Å indicating that a given atom tends to be paired with atoms of the opposite type. There is some concentration of Na-Na pairs at 5.0Å and K-K pairs at 6 to 7Å. Application of this method to vitreous silica (SiO₂) produces two independently obtained distributions that differ considerably because of the different relative magnitudes of the scattering amplitudes of the two atom types for each of the forms of radiation. The calculated ratio of the two experimental curves clearly establishes that each of the first three peaks in the atomic distribution represents a single type of atom pairing: Si-O pairs with a 1.6Å interatomic separation, O-O pairs at 2.6Å, and Si-Si pairs at 3.1 to 3.2Å. The distribution function peak for larger separations represent mixtures of all three types of pairing. The successful application of the two-pattern method to a true liquid alloy (NaK) and to an amorphous material (fused SiO₂) demonstrates its validity for determining correlation in binaries, or for testing theoretical models.

* Purdue University, West Lafayette, Indiana.

J. IRRADIATION EFFECTS AND DEFECTS IN METALS

1. Migration and Coalescence of Gas Bubbles in Solids (E. E. GRUBER)

Several copper samples have been irradiated in order to introduce gas bubbles for experimental investigation. A stack of ten thin foils (<0.001 in. thick) of pure (99.999%) copper has been irradiated in the cyclotron with α -particles, doubly charged, which are at energies of 28 and 31 MeV. These foils will be used for exploratory work to observe the helium bubbles that should form at the ends of the ranges. Several features are of interest, including the distribution of the bubbles in relation to dislocations and grain boundaries, the variation in bubble size and number with dose and post-irradiation annealing treatment, and escape of the bubbles from the foils by bubble migration, as well as the individual bubble morphologies. These studies will be carried out by transmission-electron microscopic observations of electrothinned portions of the foils.

Single crystals of copper have also been grown in the form of discs $\frac{3}{8}$ in. in diameter and $\frac{1}{8}$ in. thick. Three of these specimens have been irradiated with 140 keV α -particles in the Cockcroft-Walton accelerator, to produce a thin layer of helium bubbles near the irradiated surface. These specimens will be heated in a thermal gradient in an attempt to induce migration into the copper; observation of the migration as a function of bubble size, temperature, and thermal gradient

will then be attempted by sectioning, replicating, and electron microscope observation.

A thermal-gradient furnace, modeled after one constructed at Oak Ridge National Laboratory,⁽⁴¹²⁾ has been assembled in a bell-jar vacuum system. The principle of the furnace is quite simple; heat flows from a high-temperature molybdenum core through the sample to a water-cooled base-plate. The mean temperature and thermal gradient in the sample are obtained by the insertion of appropriately selected thermal resistors and by control of the core temperature. Pole pieces are used to improve the linearity of the heat flow, and temperatures at the ends of the sample are measured in terms of calibrated contact potentials of refractory metal foils. A counterbalancing arrangement has been added to reduce the load on the sample to a small and constant value. Further modification and calibration are underway.

The vacuum system has been modified so that it can be used for other experiments as well as for the thermal-gradient furnace. The particular objective of this versatility and portability was to provide an adequate vacuum system for use with the cryostat to be used in the low-temperature radiation-damage recovery experiment.

⁽⁴¹²⁾ Biermann, W., Heitkamp, D., and Lundy, T. S., *Acta Met.* **13**, 71 (1965).

2. Irradiation-Induced Defect Clusters in Copper and Gold. Electron Microscopy (K. L. MERKLE)

Publications

K. L. Merkle and L. R. Singer, *Radiation Annealing in Gold near 4.2°K*, *Bull. Am. Phys. Soc.* **11**, 209 (1966) [Abstract].

K. L. Merkle, *Radiation-Induced Point Defect Clusters in Copper and Gold, Part I*, *Phys. Stat. Sol.* **18**, 173 (1966).

The work on the black spot defects and the displacement cascades has been continued. A number of heavy-ion bombardments of copper and gold and also of nickel have been performed. The results on gold fit the previously established model, in which a visible black spot is produced spontaneously when the primary energy

exceeds a certain threshold energy E_T . Figure 272 shows the reduced cross section for black spot formation in the case of α - and proton-bombardment of copper. Here the experimental data do not fit a simple threshold curve. The three dashed curves in Figure 272 represent the theoretical cross sections for three different threshold energies in a sharp threshold model. Apparently none of these curves fits the data points, nor do curves corresponding to intermediate threshold energies. However, if one multiplies the cross sections corresponding to a threshold energy $E_T = 10$ keV with a factor of 0.1, one gets a reasonable fit with the experimental data (heavy line). Copper also shows, in contrast to gold, only very small defect clusters: 98% of the

44579

FIG. 272. The Reduced Cross Section σ'_s for Black Spot Formation in Copper as a Function of the Maximum Primary Energy.

clusters have a diameter smaller than 40 Å. This and the results on the cross sections for spot formation can be explained by the model of collision cascades in copper depicted in Figure 273. Here we see a schematic representation of the defect arrangement in collision cascades of copper of two different primary energies. The displacement cascade is split up into subcascades at relatively low energies. Vacancy clusters are formed in the subcascades; however, the clusters are generally too small to be visible in the electron microscope (< 10 to

20 Å). Only if two or more subcascades overlap or if they are close enough to collapse into a single cluster is the cluster large enough to be visible by transmission electron microscopy. This of course occurs with a probability smaller than one even for cascades whose energy is large enough to produce a sufficient number of vacancies.

143234

FIG 273 A Schematic Representation of the Defect Arrangement in Collision Cascades of Copper of Different Primary Energy E_p .

3. Low-Temperature Charged-Particle Irradiations of Thin Films

(K. L. MERKLE AND L. R. SINGER)

Measurement of the changes in electrical resistivity that occur upon irradiation has been a major technique in the investigation of radiation-induced defects. However, with macroscopic samples one is severely limited in the choice of maximum recoil energies T_m . The electron irradiations are limited to values of T_m below a few 100 eV and the cyclotron and neutron irradiations have T_m greater than 10^5 eV. The gap in between those energies is particularly interesting because it is associated with the onset of large cascade events, which, for example, produce the black-spot defects. Our efforts have concentrated on this intermediate energy range,

which can be achieved with proton and α -irradiations in the keV and MeV ranges; but the specimens have to be extremely thin ($\sim 10^{-5}$ cm) in order to avoid energy degradation of the particle beam. Much of our effort during the past year was still concerned with the particular problems that arise from the use of thin-film specimens. One of the problems is the contribution of the surface scattering to the electrical resistivity. This surface scattering is present in addition to the scattering from the radiation-induced defects and one has to allow for this in order to make conclusions regarding the bulk-resistivity change. According to the

46391

FIG. 274. The Ratio between a Change in Bulk Resistivity and the Corresponding Change in Resistivity Observed in a Thin Film as a Function of $\gamma\rho_\infty$. By multiplying the damage rate observed in a thin film with $d\rho_\infty/d\rho$ one gets the damage rate in the bulk material $d\rho_\infty/d\phi$.

Fuchs-Sondheimer theory⁽⁴¹³⁾ the ratio between thin-film resistivity, ρ , and bulk resistivity, ρ_∞ , is given by

$$\frac{\rho}{\rho_\infty} = \frac{\phi_p(y)}{y} \quad \text{with} \quad y = \frac{a}{\lambda} \quad (1)$$

Where a is the film thickness and λ the mean free path of the electrons. The function ϕ_p is given by

$$\phi_p(y) = \left[\frac{1}{y} - \frac{3}{2y^2} (1-p) \int_1^\infty \left(\frac{1}{t^3} - \frac{1}{t^5} \right) \cdot \frac{1 - e^{-yt}}{1 - pe^{-yt}} dt \right]^{-1}$$

where p is the specular reflection coefficient at the surface with $0 \leq p \leq 1$. According to the free electron theory $\lambda\rho_\infty = c$ is a constant for any given metal, regardless of the defect concentration. For expression (1) we now get

$$\gamma\rho = \phi_p(\gamma\rho_\infty) \quad \text{where} \quad \gamma = \frac{a}{c}$$

Miss Janet Herman of AMD, Argonne National Laboratory, has written a computer program that allows us to correct our data for the size effect. An

⁽⁴¹³⁾ Sondheimer, E. H., Adv. Phys. I, 1 (1952).

important quantity in radiation damage experiments is the damage rate.

Figure 274 shows the correction factors to the measured-damage rate for different values of p as a function $\gamma\rho_\infty$. The correction factor obviously can be greater or smaller than 1, depending upon the defect concentration. In very thin films and at low defect concentrations the observed-damage rate can be a factor of five or more higher than what the rate would be in a bulk sample. The main problem in connection with this is at present the accurate determination of the constants γ and p . So far we have been forced to use only approximate values to make the corrections.

Supplementary to the preliminary measurements on copper and gold as reported last year we have been able to make more accurate measurements on these metals. The enhanced decrease of the damage rate at low defect concentrations is still present even after application of the surface correction; however, the effect is not as pronounced as it would appear from the uncorrected data. We have also been able to study the electrical-resistivity changes of thin films of aluminum under 2 MeV α -irradiation. In this case the saturation seems to be simply exponential. Figure 275 shows that the corrected data fit reasonably well a straight line in the $d\Delta\rho/d\phi$ vs. $\Delta\rho$ -plot. We have also included in Figure 275 the uncorrected data. It can be seen that the apparent damage rate in a thin film is initially about a factor of two higher than the actual one. Extrapolation to zero damage rate gives $\Delta\rho_\infty = 0.88 \times 10^{-6} \Omega \text{ cm}$, which is in good agreement with the value found in neutron irradiations. This is not surprising because

46226

FIG. 275. The Decrease in the Damage Rate in a Thin Film of Aluminum. The corrected values are approximately on a straight line.

142770

320000X

FIG. 276. The Electron Micrograph Shows a Gold Film That Has Been Irradiated at 4.2°K with 2 MeV α -particles to a Total Dose of $4.4 \times 10^{16} \alpha/\text{cm}^2$. After warm up to room temperature the specimen, which had originally a thickness of 6500 Å was electrothinned. The thickness of the area viewed ranges from 0 (at the hole) to about 200 Å. Near the edge of the large hole some defects have been the cause for small etch pits and tiny holes.

one can expect that in aluminum mainly individual Frenkel pairs will be formed under neutron irradiation as well as in charged-particle irradiations, and the saturation behavior is therefore also not expected to be different. After irradiation at 4.2°K to a dose of $4.4 \times 10^{16} \alpha/\text{cm}^2$ the specimen was examined in the electron microscope and no evidence for clusters larger than 20 Å was found. In contrast to this we find black spot clusters in gold after irradiation at 4.2°K and warm-up to room temperature. Figure 276 shows an example of this. At present we are evaluating these data to correlate the $\Delta\rho$ that is left after an anneal to room temperature with the density of defect clusters as observed by transmission electron microscopy. Isochronal annealing experiments on the black-spot damage in gold have

shown recently that 50 % of the spots are annealed out at 255°C. It is planned to correlate this with experiments on the effects of annealing on the electrical resistivity. The energy dependence of the ratio of theoretical to experimental damage production, as mentioned in last year's report (ANL-7155, pp. 257-259), seems to be real. However we were only able to perform one experiment to further investigate this. This time the measurements were made on the same specimen and the beam was changed from alpha particles to protons while the specimen was kept at 4.2°K. It is thought that this effect is related to the anisotropy of the threshold energy for displacement. A cryostat is now under construction that will allow the investigation of angular effects.

4. Recovery of Lattice Parameter and Electrical Resistivity in Low-Temperature Neutron-Irradiated Copper (E. E. GRUBER AND J. A. TESK*)

The purpose of this experiment is to investigate the nature of the recovery processes occurring in neutron-irradiated copper at low temperatures. Although electrical-resistivity measurements can be used to measure the number of defects removed during annealing, the defect type is not distinguishable and leads to a certain amount of controversy. On the other hand, lattice-parameter measurements enable one to distinguish between the defects being removed, since vacancies decrease the lattice parameter slightly while interstitials cause an increase in lattice parameter. Some ambiguity

accurate data to permit step-by-step comparison of the small changes to be measured. These difficulties arise primarily from the difficulty in accurately reproducing the irradiation and annealing conditions in two separate experiments.

The approach in this experiment is to simultaneously measure the recovery of resistivity and lattice parameter following irradiation at 4.2°K. This approach makes the experiment considerably more complex than if each parameter were measured separately. Briefly, the experiment consists of aligning a capsule (containing two samples and auxiliary apparatus) in a cryostat on a spectrometer, removing and irradiating the capsule at 4.2°K, storing the capsule in a dewar of liquid helium for one week to allow the radioactivity to decay, then replacing and realigning the capsule in the spectrometer cryostat, still at 4.2°K. The annealing will then be carried out by pulse heating to successively higher temperatures and measuring the resistivity and lattice parameter at 4.2°K after each pulse. The analysis will be based on the manner in which a plot of resistivity recovery as a function of lattice parameter recovery deviates from a straight line in the regions corresponding to the various recovery peaks.

The key component of the apparatus is the titanium "cryocapsule," which resembles a small dewar with a demountable bottom section. (See Figure 277.) Two specimens, a thin wire for resistivity measurements and a single crystal for lattice-parameter measurements, are mounted in the cryocapsule on a copper specimen holder so that the irradiation and annealing histories of the specimens will be as nearly identical as possible. The wire (with current and potential leads attached), a thermocouple and carbon resistor for temperature measurements, and resistance heaters are mounted inside the cryocapsule with leads extending out the top. The single crystal is mounted on the bottom of the specimen holder, inside the vacuum jacket. The bottom of the vacuum jacket is designed so that it can be removed after the cryocapsule is remounted in the cryostat, in order to expose the crystal to the X-ray beam, which will pass through a mylar window in the cryostat.

The cryocapsule was initially designed with a short length of copper tubing electron-beam welded to the inner wall of titanium, to facilitate soldering the specimen holder into the cryocapsule. The beam-welded joint failed after preliminary thermal cycling, however, due to brittle intermetallics in the weld zone, and it was necessary to replace the copper section with a titanium section. It became necessary to devise a

46107

FIG. 277. Cryocapsule with Specimen Holder and Specimen Cover in Place.

remains in the interpretation of lattice parameter recovery, however, because certain combinations of vacancy and interstitial removal should result in no net change in lattice parameter, so that the number of defects removed in a particular anneal is unknown. One might attempt to measure these two properties in two completely separate experiments and attempt to correlate the results to determine the atomistic processes responsible for the various portions of the recovery spectrum. This approach is not feasible, however, because of the difficulty in obtaining sufficiently

* University of Illinois, Chicago Circle, Consultant to Metallurgy Division.

means of soldering the copper specimen holder to the titanium. This was accomplished by induction-melting silver over the end of the titanium tube, then soldering to the silver. The joint has been found to be helium leak-tight after a number of thermal cycles.

The equipment needed for the experiment has been obtained and assembled. An X-ray table has been constructed and the spectrometer and X-ray tube have been mounted on the table. The helium cryostat has been mounted on the spectrometer and counterbalanced, and the counter tube (a proportional counter) has been mounted on the spectrometer. Specimens have

been mounted in the cryocapsule and oriented by Laue techniques on the spectrometer. The only remaining equipment need is the installation of a voltage stabilizer for the X-ray tube power supply; this should be installed within two weeks.

Preliminary experiments will then be carried out to measure the lattice parameter and electrical resistivity of the undamaged specimens, followed by "dry run" testing of the pulse heating techniques. Upon successful completion of the preliminary tests, the cryocapsule will be inserted in the reactor and the experiment will begin.

5. Low-Temperature Energy Release in Irradiated Copper (M. W. LUCAS)

The stored-energy release and resistivity recovery associated with Stage I annealing of neutron-irradiated copper have been successfully measured. In the temperature range 35 to 48°K the ratio of the energy release to resistivity change was $3.8 \pm 0.5 \text{ cal gm}^{-1} (\mu\Omega \text{ cm})^{-1}$.

The compensated-gas thermometer designed to measure time-temperature curves was described in ANL-7000. The copper specimen used to study energy release weighed about 60 gm and was made the bulb of the gas thermometer. One end of the resistivity specimen, a 0.040 cm diameter copper wire made from the same 99.999% pure copper as the bulb, was soft-soldered to the bottom of the bulb. This wire ran alongside the bulb to a point just above the top of the bulb where it was soldered to a constantan lead wire. The current circuit to the resistivity sample was therefore completed through the thermometer to ground. No. 43 gauge copper potential leads were soldered to the resistivity specimen near the top and bottom of the bulb. The specimen was insulated with inorganic paint and tied to the bulb with two No. 43 copper wires.

The hydrogen-helium heat switch described by Blewitt *et al.*⁽⁴¹⁴⁾ provided sufficient heat transfer to the cryostat in Hole VT-53 to maintain a specimen temperature of 29°K at 2 Mw reactor power. This temperature was not low enough to prevent some Stage I annealing during irradiation; however, after irradiating B¹⁰ doped copper with thermal neutrons Blewitt observed the energy release below 38°K to be small.

During irradiation the resistivity of the wire specimen increased at a rate of $1.67 \times 10^{-25} \Omega \text{ cm}$

$\text{n}^{-1} \text{ cm}^{-2}$ ($E > 1.0 \text{ MeV}$). This was at 29°K and was 90% of the rate observed by Horak⁽⁴¹⁵⁾ for pure copper of similar dimensions irradiated at 4°K in Hole VT-53. Horak⁽⁴¹⁶⁾ has also obtained isochronal annealing data for copper irradiated at 4°K, Figure 278. At 29°K the resistivity remaining was 94% so that more recovery took place during irradiation at 29°K than would be expected from thermal annealing alone.

After an irradiation of about six days the reactor power was lowered to 200 kw. The specimen temperature dropped to an equilibrium value of 14.5°K and the resistance of the wire was measured. When the heat switch was opened the γ -radiation produced at 200 kw was sufficient to heat the specimens at a rate of 1 to 2°K min^{-1} in the range 35 to 50°K. A time-temperature curve was recorded continuously from 16 to 60°K. The specimens were recooled to 14.5°K the resistance remeasured and a second time-temperature curve taken at 200 kw. The specimens reached a maximum of 72°K between the two runs. The differential time-temperature curves are shown in Figure 279.

The energy release is given by Blewitt⁽⁴¹⁴⁾ as:

$$E = \int \gamma \left\{ \left(\frac{dt}{dT} \right)_{\text{Run 2}} - \left(\frac{dt}{dT} \right)_{\text{Run 1}} \right\} dT$$

where γ , the nuclear heating, can be obtained by comparing Run 2 with the specific heat data of, Giauque and Meads.⁽⁴¹⁷⁾ This is done in Table 99. Between 35 and 60°K γ varies from a mean value of $2.46 \text{ cal mol}^{-1} \text{ sec}^{-1}$ by less than 2%. This ability of the experiment to predict the correct temperature de-

⁽⁴¹⁵⁾ Horak, J. A., ANL-7155, pp. 260 to 263 (1965).

⁽⁴¹⁶⁾ Horak, J. A., ANL-7185, p. 303 (1966).

⁽⁴¹⁷⁾ Giauque, W. F., and Meads, P. F., J. Am. Chem. Soc. **63**, 1897 (1941).

⁽⁴¹⁴⁾ Blewitt, T. H., Coltman, R. R., and Klabunde, C. S., J. Phys. Soc. of Japan, **18**, Suppl. III (1963).

45950

FIG. 278. Isochronal Annealing Data for Neutron-irradiated Copper (after Horak).

pendence of the specific heat, when no stored energy is present, is valuable confirmation that heat leaks are negligible. The measured-energy release E was $1.6 \pm 0.1 \times 10^{-2} \text{ cal gm}^{-1}$.

The resistivity recovery during Run 1 was $5.7 \times 10^{-3} \mu\Omega \text{ cm}$. This occurred during an anneal from 29°K (the temperature of irradiation) to 72°K but stored energy was only observed in the interval 35 to 48°K . The fraction of the measured resistivity recovery, which should be compared with the stored energy release, can be estimated from Horak's data in Figure 278. In the interval 35 to 48°K the fractional resistivity remaining drops from 0.89 to 0.70 , whereas from 29 to 72°K , it drops from 0.94 to 0.66 . There is some uncertainty about using the value 0.94 since the observed damage production rate was only 0.90 of Horak's. This is included as an error below so that the resistivity change to compare with the energy release is:

$$\Delta\rho = \frac{0.89 - 0.70}{0.92 - 0.66} \times 5.7 \times 10^{-3} \\ = 4.2 \pm 0.3 \times 10^{-3} \mu\Omega \text{ cm}.$$

The ratio of energy release to resistivity recovery is therefore $3.8 \pm 0.5 \text{ cal gm}^{-1} (\mu\Omega \text{ cm})^{-1}$ in agreement

45949

FIG. 279. Differential Time-Temperature Curves for Copper.

TABLE 99. NUCLEAR HEATING AS A FUNCTION OF TEMPERATURE

Temperature (°K)	Specific Heat C_p (cal mol ⁻¹ °K ⁻¹ (a))	dt/dT (sec °K ⁻¹)	$\gamma = C_p/(dt/dT)$ (cal mol ⁻¹ sec ⁻¹)
20	0.114	6.7	1.70
25	0.233	11.5	2.02
30	0.412	18.0	2.31
35	0.637	26.2	2.43
40	0.901	36.1	2.50
45	1.191	48.0	2.48
50	1.493	60.6	2.46
60	2.074	86.2	2.41

(a) After Giauque and Meads.

with Blewitt's^(414,418) results but not with those of Nilan and Granato⁽⁴¹⁹⁾ [$7.1 \text{ cal gm}^{-1} (\mu\Omega \text{ cm})^{-1}$] or

⁽⁴¹⁸⁾ Blewitt, T. H., *Low-Temperature Irradiation Studies*, Proceedings of the International School of Physics, E. Fermi XVIII Corso, "Radiation Damage in Solids," pp. 630 to 71 Academic Press, New York and London (1962).

⁽⁴¹⁹⁾ Nilan, T. G., and Granato, A. V., *Phys. Rev.* **137A**, 1233 (1965).

Heeger *et al.*⁽⁴²⁰⁾ The latter two groups use differential calorimetry and Heeger *et al.* have suggested Blewitt made a wrong estimate of systematic errors.

To determine if this was the case a dummy experiment was run in which stored-energy release was simulated by an electrical heater. The original experimental rig was used with a small cal rod heater (0.032 in. dia. x 0.50 in. long) soldered to the copper bulb. The copper bulb was heated as in the stored-energy experiment by nuclear heating from 200-kilo-watt reactor power. When the temperature reached

35°K, 1.10 cal mole⁻¹ of heat was supplied by the cal rod in a period of 500 sec. This amount of heat and time interval corresponded to that of the energy release of the irradiated bulb. The data were handled as before and the area as determined from the dt/dT vs T curves showed an energy of 0.94 cal mole⁻¹.

This latter experiment has shown that with the calorimetry used here the stored energy of neutron-irradiated samples can be measured to within 15%. This, coupled with the fact that the temperature dependence of the specific heat is correctly predicted within the range of interest, is strong evidence for the accuracy of this value, 3.8 ± 0.5 cal gm⁻¹ ($\mu\Omega$ cm)⁻¹.

⁽⁴²⁰⁾ Heeger, D., Rau, F., Tischer, P., and Wenzl, H., Phys. Letters **21**, 393 (1966).

6. Energies and Atomic Configurations of Defects in fcc Metals

(R. M. J. COTTERILL* AND M. DOYAMA†)

Publications

- R. M. J. Cotterill, *A Brief Review of Energy Calculations for Clusters of Point Defects in Metals*, AERE-R 5269, I, Report of Consultants' Symposium, AERE, Harwell, England, July 4-7, 1966, 144-172 (1966).
- R. M. J. Cotterill and M. Doyama,† *A Study of Small Vacancy Clusters on {111} Planes in Copper*, AERE-R 5269, I, Report of Consultants' Symposium, AERE, Harwell, England, July 4-7, 1966, 211-217 (1966).
- R. M. J. Cotterill and M. Doyama,† *Investigation of the Stability of Voids in fcc Metals*, Bull. Amer. Phys. Soc. II, **11**(1), 48 (1966) [Abstract].
- R. M. J. Cotterill and M. Doyama,† *Binding Energies of Vacancy Clusters in Copper*, Bull. Amer. Phys. Soc. **11**(4), 460 (1966) [Abstract].
- R. M. J. Cotterill and M. Doyama,† *Oscillatory Potential Calculations of the Vacancy Formation Energy in Aluminum*, Bull. Amer. Phys. Soc. **11**(3), 416 (1966) [Abstract].
- R. M. J. Cotterill and M. Doyama,† *Atomistic Approach to the Peierls-Nabarro Barrier for Edge Dislocations*, Bull. Amer. Phys. Soc. **11**(3), 346 (1966) [Abstract].
- R. M. J. Cotterill and M. Doyama,† *The Energy and Atomic Configuration of Complete and Dissociated Dislocations. I. Edge Dislocation in an fcc Metal*, Phys. Rev. **145**, 465-478 (1966).

R. M. J. Cotterill, *A Comparison Between Neutron Damage in Annealed Gold and in Quenched Gold*, Appl. Phys. Letters **9**, 29-31 (1966).

R. M. J. Cotterill and M. Doyama,† *Atomic Configuration and Energy of Edge Dislocations in bcc Metals*, Bull. Amer. Phys. Soc. **11**(2), 219 (1966) [Abstract].

F. W. de Wette,‡ R. M. J. Cotterill, and M. Doyama,† *Lattice Dynamics of Copper with a Morse Potential*, Phys. Letters **23**, 309-311 (1966).

F. W. de Wette,‡ R. M. J. Cotterill, and M. Doyama,† *Lattice Dynamics of fcc Crystals with a Morse Potential*, Bull. Amer. Phys. Soc. **11**(2), 249 (1966) [Abstract].

M. Doyama† and R. M. J. Cotterill, *Energy and Atomic Configurations of Complete and Dissociated Dislocations. II. Screw Dislocation in an fcc Metal*, Phys. Rev. **150**, 448-455 (1966).

M. Doyama† and R. M. J. Cotterill, *Vacancy-Impurity Binding Energy in Aluminum*, Phys. Letters **23**, 58-59 (1966).

M. Doyama† and R. M. J. Cotterill, *Investigation of Metallic Surfaces in the Central Force Approximation*, Bull. Amer. Phys. Soc. **11**(2), 250 (1966) [Abstract].

M. Doyama† and R. M. J. Cotterill, *Atomic Configuration and Energy of Screw Dislocations in bcc Metals*, Bull. Amer. Phys. Soc. **11**(4), 460 (1966) [Abstract].

M. Doyama† and R. M. J. Cotterill, *Peierls-Nabarro*

* Spending the academic year 1966-1967 at the Technical University of Denmark, Lyngby, Lundtofte, Denmark.

† With the Solid State Science Division, ANL.

‡ Department of Physics, University of Texas, Austin, Texas.

125-2412

FIG. 280. Arrangements of Vacancies on $\{111\}$ Planes for Compact Clusters of Various Sizes.

125-2413

FIG. 281. Formation Energy of Clusters of Various Sizes as a Function of Size.

Barrier Calculations for Screw Dislocations, Bull. Amer. Phys. Soc. **11**(3), 416 (1966) [Abstract].

M. Doyama† and R. M. J. Cotterill, *Frenkel Pairs in fcc Metals*, Bull. Amer. Phys. Soc. **11**(3), 346 (1966) [Abstract].

M. Doyama† and R. M. J. Cotterill, *Application of Oscillatory Potentials to Atomistic Calculations of Lattice Defects*, Bull. Amer. Phys. Soc. II, **11**(1), 48 (1966) [Abstract].

T. J. Koppenaal, W. C. T. Yeh,§ and R. M. J. Cotterill, *Lattice Defects in Neutron Irradiated α Cu Solid Solution Alloys*, Phil. Mag. **13**, 867 (1966).

The work on lattice defects, considered on the basis of atomistic models and the central force approximation, is continuing. The calculations are carried out on the ANL CDC 3600 computer. Clusters of vacancies larger than the tetravacancy have now been examined.

Figure 280 shows several compact arrangements of vacancies on a single $\{111\}$ plane in the fcc lattice. The clusters have various shapes, of which the triangle and the hexagon are particularly interesting because these correspond to the shapes of large defects that have been observed by transmission electron microscopy. The smallest triangle is the 60° trivacancy, which was studied by Dienes, Damask and Weizer.⁽⁴²¹⁾ The atom immediately above the three vacancies that undergoes the large relaxation discussed earlier is shown by the small black circle. (This convention is used throughout to represent relaxing atoms that are initially located in the plane immediately above the plane containing the vacancies. The corresponding atoms in the plane underneath the vacancies have been omitted for the sake of clarity.) The next larger complete triangle contains six vacancies, and the next one larger than that has ten vacancies. One of these clusters, possibly even the one containing only three vacancies, might be the nucleus of the stacking-fault tetrahedron, as was discussed by de Jong and Koehler.⁽⁴²²⁾ The smallest complete hexagon has seven vacancies, and the next larger size contains nineteen vacancies. Large vacancy clusters in quenched aluminum are frequently hexagonal in shape.⁽⁴²³⁾ If all the vacancies lie on a single $\{111\}$ plane, then the shape of the cluster is unique for all clusters containing five vacancies or less, if every vacancy is the nearest

§ Michigan Technological University, Houghton, Michigan.

⁽⁴²¹⁾ Dienes, G. J., Damask, A. C., and Weizer, V. G., Phys. Rev. **113**, 781 (1959).

⁽⁴²²⁾ de Jong, M., and Koehler, J. S., Phys. Rev. **129**, 40 (1963).

⁽⁴²³⁾ Cotterill, R. M. J., and Segall, R. L., Phil. Mag. **8**, 1105 (1963).

neighbor of at least two other vacancies. For six vacancies a choice arises between the triangle and a defect that has four sides of a hexagon. Similarly, for seven vacancies, one can have a complete hexagon or a triangle with an extra atom attached to one of its sides. For larger clusters the number of choices increases with the number of vacancies in the cluster. In the present study only the configurations shown in Figure 280 were examined.

The results that have been obtained so far in this study are shown in Figure 281. Figure 281 shows that the cluster energy rises monotonically with n , the number of vacancies until n is 4. The trapezoidal pentavacancy has a lower energy than the rhombic tetravacancy even though it contains one more vacancy. This trend is continued for $n = 6$, but here the fact that one has a choice between a complete triangle and incomplete hexagon complicates the issue. The triangular form has the lower energy. In the triangular arrangement three atoms immediately above the six vacancies relax downwards in the same way. This introduces an important principle, namely that when three relaxing atoms from a triangle on a $\{111\}$ plane, and an atom from the plane above will relax toward this triangle, and an increased lowering of energy will arise from this third layer relaxation. Similarly, the

triangle with ten vacancies, and four vacancies on any one side, gives rise to additional fourth-layer relaxations. In general, a triangle with m vacancies on a side gives rise to large relaxations in the m atomic layers above it. In each case the resultant defect is symmetrical with respect to the four $\{111\}$ planes and is in fact a stacking-fault tetrahedron.

The early results shown in Figure 281 show that the energy per cluster first rises with the number of vacancies in the cluster and then decreases, at least for the triangular and hexagonal configurations. For larger clusters, the curve must, of course, increase steadily with n . The reason for the intermediate region in which the decrease occurs appears to be due to the importance of relaxations for small clusters. For such clusters it is probably not meaningful to discuss the energy in terms of energy contributions due to dislocations and stacking faults. In fact, for such small sizes faults and dislocations probably cannot exist in the form that they would take in large defects.

Above $n = 5$ and until the as yet undetermined point where the curve again begins to rise, the total energy required to detach one vacancy from a cluster is anomalously high. This suggests that the nucleus of a vacancy cluster has a size that is somewhere in this range.

7. Lattice Dynamics of fcc Crystals with a Morse Potential

(R. M. J. COTTERILL* AND D. W. DE WETTE†)

The Morse potential has been extensively used as an effective interionic pair-potential in metals in calculations of the formation and migration of defects.⁽⁴²⁴⁾ To test the validity of the Morse potential for obtaining dynamic and thermodynamic properties of metals, this potential, with constants derived from static bulk crystal properties, was used in lattice dynamics calculations for copper in the quasi-harmonic approximation. The calculations were analogous to those carried out earlier for the noble gas solids.⁽⁴²⁵⁾

* Spending the academic year 1966–1967 at the Technical University of Denmark, Lyngby, Lundtofte, Denmark.

† Department of Physics, University of Texas, Austin, Texas.

⁽⁴²⁴⁾ Cotterill, R. M. J., and Doyama, M., *Bull. Am. Phys. Soc.* **10**, 78, 323, 618, 689, 1095 (1965).

⁽⁴²⁵⁾ de Wette, F. W., and Nijboer, B. R. A., *Bull. Am. Phys. Soc.* **10**, 293 (1965); Nijboer, B. R. A., and de Wette, F. W., *Physics Letters* **17**, 256 (1965).

The vibration frequencies $\omega(q, j)$ and polarization vectors were determined for 1505 q -values in the irreducible part (1/48th) of the Brillouin zone, for 61 different lattice parameters, corresponding to densities of copper between -200 and $+400^\circ\text{C}$. (See Figure 282.) The thermal expansion was obtained by minimizing the free energy with respect to the lattice parameter for a number of temperatures in this range. The specific heat C_V and Debye temperature (see Figure 283) were calculated for these same temperatures. All calculated quantities compare very favorably with experimental results.^(426,427)

⁽⁴²⁶⁾ Sinha, S. K., *Phys. Rev.* **143**, 422 (1966); Nicklow, R. M., Gilat, G., Smith, H. G., Raubewheimer, L. J., and Wilkinson, M. K., *Bull. Amer. Phys. Soc.* **11**, 263 (1966).

⁽⁴²⁷⁾ Giauque, W. F., and Meads, P. F., *J. Amer. Chem. Soc.* **63**, 1897 (1941).

125-2470 Rev. 2

FIG. 282. Phonon Dispersion Curves for Cu along the Three Major Symmetry Directions.

125-2468 Rev. 2

FIG. 283. Temperature Variation of the Debye Temperature for Cu.

8. Effect of Low-Temperature Irradiation on Precipitation in Al-Zn Alloys (J. A. HORAK)

Publication

J. A. Horak and T. H. Blewitt, *Effect of Irradiation on Precipitation in Al-Zn Alloys*, Bull. Am. Phys. Soc. **11**, 210 (1966) [Abstract].

High-purity Cu, Al, Al-1.70a/oZn, Al-3.41a/oZn and Al-5.27a/oZn were irradiated at 7°K in the CP-5

reactor fast flux facility. Before the irradiation the Al-Zn alloy specimens were reverted *in situ* at 440°K whereas previously this was done at 400°K.⁽⁴²⁸⁾ The higher reversion temperature was used to insure complete reversion of the Guinier-Preston zones formed

⁽⁴²⁸⁾ ANL-7155, 262 to 263 (1965).

43906

FIG. 284. Resistivity Change as a Function of Isochronal Annealing Temperature for Reverted and Reverted-irradiated Al-1.70% Zn and Al.

during the 650 minutes of isothermal aging at 290°K. The samples were irradiated to a dose of 2×10^{17} n/cm² of $E > 1.0$ MeV. Following the low-temperature bombardment the samples were isochronally annealed to 80°K *in situ* and removed from the reactor. During the removal operation the sample temperature did not exceed 100°K. Isochronal anneals were then made to 400°K.

The migration of interstitial atoms during post-irradiation Stage I annealing (4.2°K to 50°K) did not result in the clustering of zinc atoms to form G.P. zones. The electrical resistivity of the Al-Zn alloys exhibited a continual decrease during Stage I that is similar to the Stage I recovery of copper containing small concentrations of gold.⁽⁴²⁹⁾ In addition during Stage II annealing (50°K to 150°K) only a continued resistivity decrease occurred. Guinier-Preston zone formation with its associated resistivity increase did not begin until the beginning of Stage III annealing in aluminum at about 160°K.

Figures 284, 285, and 286 and Table 100 show the large irradiation-induced enhancement of zone formation. From the magnitude of the resistivity maximum it can be seen that in the Al-3.41a/oZn and the Al-5.27a/oZn alloy irradiation caused between two and three times as many zones to form in the reverted samples.

In the figures the resistivity change of the pure aluminum is shown to indicate the resistivity recovery

⁽⁴²⁹⁾ Blewitt, T. H., Coltman, R. R., Klabunde, C. E., and Noggle, T. S., J. Appl. Phys. **28**, 639 (1957).

associated with only the annihilation of the irradiation-induced lattice defects.

Figure 287 shows the increase in resistivity due to the formation of G.P. zones in the Al-5.27a/oZn alloy in the quenched state and in the quenched and irradiated state. Comparing Figures 286 and 287 we see that, for this alloy, irradiation has resulted in more zones being formed in reverted material than in

43907

FIG. 285. Resistivity Change as a Function of Isochronal Annealing Temperature for Reverted and Reverted-irradiated Al-3.41% Zn and Al.

43908

FIG. 286. Resistivity Change as a Function of Isochronal Annealing Temperature for Reverted and Reverted-irradiated Al-5.27% Zn and Al.

TABLE 100. ISOCHRONAL ANNEALING BEHAVIOR OF
REVERTED AND REVERTED-IRRADIATED Al-Zn
ALLOYS

Material	Treatment	Start of Aging (°K)	T_{max} (°K)	$\Delta\rho_{max}$ ($10^{-9} \Omega$ cm)
Al-1.70a/oZn	Reverted at 440°K	240	296	5.35
"	Reverted at 440°K and Irradiated	218	243	6.44
"	Reverted at 440°K	240	296	5.18
"	Reverted at 440°K and Irradiated	218	243	5.73
Al-3.41a/oZn	Reverted at 440°K	240	314	36.87
"	Reverted at 440°K and Irradiated	190	253	115.98
"	Reverted at 440°K	240	314	30.61
"	Reverted at 440°K and Irradiated	190	253	113.35
Al-5.27a/oZn	Reverted at 440°K	240	314	105.10
"	Reverted at 440°K and Irradiated	164	253	216.27
"	Reverted at 440°K	240	314	117.02
"	Reverted at 440°K and Irradiated	164	253	212.71

43905

FIG. 287. Resistivity Change as a Function of Isochronal Annealing Temperature for As-Quenched and As-Quenched-irradiated Al-5.27% Zn and Al.

material; and almost as many zones were formed in reverted and irradiated samples as in quenched and irradiated samples. This, plus the fact that the temperature of the beginning of zone formation and the temperature of the resistivity maxima during isochronal annealing were functions of defect concentration, suggests that formation of G.P. zones in Al-Zn alloys is controlled by the point-defect concentration.

The point-defect concentrations were calculated after reversion and after irradiation in an attempt to relate the temperature shift of the resistivity maxima to the point-defect concentrations produced by these treatments. In the first method the point-defect concentration as a function of isochronal annealing temperature for the irradiated samples was calculated by dividing the irradiation-induced resistivity remaining at the temperatures of interest by the resistivity of a Frenkel pair in aluminum.* Based on the value of $3 \times 10^{-4} \Omega$ cm/atom fraction of vacancies in aluminum by Simmons and Balluffi⁽⁴³¹⁾ a value of $6 \times 10^{-6} \Omega$ cm/atom fraction of Frenkel pairs was utilized.

The Meechan-Brinkman⁽⁴³²⁾ method for isochronal annealing curves was the second method employed. The defect concentrations calculated with the Brinkman analysis were compared with those obtained by the above method for the irradiated specimens and with those calculated by Equation (1) for the quenched specimens.

$$C_{vT} = \exp(S_{F/k}) \cdot \exp(-E_{F/kT}) \quad (1)$$

where

C_{vT} = equilibrium vacancy concentration at the reversion temperature of 440°K

$$S_{F/k} = 2.4^{(5)}$$

$$E_F = 0.77 \text{ eV}^{(5)}$$

As shown in Table 101 the irradiation-induced point-defect concentration remaining at the start of zone formation was more than adequate to account for the observed-temperature shift of the resistivity maxima.

The temperature shifts and increased heights of the resistivity maxima after irradiation are in excellent agreement with the temperature shifts and increased-peak heights obtained after quenching from increased temperatures within the solid-solution range,⁽⁴³³⁾ i.e., increased vacancy concentration. The almost one-to-one correspondence of the quenching results and irradiation results give strong evidence that the defect responsible for the enhanced-zone formation after irradiation is the lattice vacancy.

As shown in Figures 284 to 287 zone formation begins at the same isochronal annealing temperature (165°K) as the start of Stage III recovery in aluminum. It

* Even though the defects are thought to exist in clusters after fast neutron irradiation, recent calculations by Alfred⁽⁴³⁰⁾ indicate that resistivity per defect is essentially the same for defects when they are separated and when they are clustered.

⁽⁴³⁰⁾ Alfred, L. C. R., Phys. Rev. **152**, 693 (1966).

⁽⁴³¹⁾ Simmons, R. O., and Balluffi, R. W., Phys. Rev. **117**, 1046 (1960).

⁽⁴³²⁾ Meechan, C. J., and Brinkman, J. A., Phys. Rev. **103**, 1193 (1956).

⁽⁴³³⁾ Panseri, C., and Federighi, T., Acta Met. **8**, 217 (1960).

appears that the defect responsible for Stage III recovery in aluminum is also the defect responsible for G.P. zone formation in the alloys. It is well accepted that the lattice vacancy is responsible for the enhanced formation of G.P. zones after quenching. This gives strong support to the hypothesis that the lattice vacancy is the mobile defect during Stage III annealing in aluminum and Al-Zn alloys.

A very important finding (Figures 284 to 287) is that zone formation takes place at temperatures well above that where all of the irradiation-induced defects have been annihilated in aluminum. This indicates there is an attractive interaction between the zinc atoms and vacancies that gives the vacancies a much longer lifetime in the alloys than in pure aluminum; a conclusion also reached on quenching.⁽⁴³³⁾

It might be suggested that the high concentration of G.P. zones in the reverted and irradiated samples compared to the reverted samples was due to irradiation-induced nucleation sites that later became G.P. zones. To test this we must compare the number of G.P. zones/unit volume in reverted material with the number of fast neutron events/unit volume. For a dose of 2×10^{17} n/cm² there were 5×10^{16} events per cm³. For the Al-5.27a/oZn alloy in the reverted state small-angle X-ray scattering gave values from 4×10^{19} to 5×10^{20} zones per cm³ at the resistivity maximum.⁽⁴³⁴⁾

⁽⁴³⁴⁾ Herman, H., Ph.D. Thesis, Northwestern University, Evanston, Illinois, (June 1961).

TABLE 101. CALCULATED VACANCY CONCENTRATIONS FOR REVERTED AND REVERTED-IRRADIATED Al-Zn ALLOYS

Material	Temperature of Resistivity Peak (°K)	$C_v^{(a)}$	$C_v^{(b)}$	C_v Eqn. (1)
Al-1.70a/oZn Reverted	295	3×10^{-8}		3×10^{-8}
Al-1.70a/oZn Reverted and Irradiated	243	2×10^{-6}	2×10^{-5}	
Al-3.41a/oZn Reverted	314	1×10^{-8}		3×10^{-8}
Al-3.41a/oZn Reverted and Irradiated	253	1×10^{-6}	2×10^{-5}	
Al-5.27a/oZn Reverted	314	1×10^{-8}		3×10^{-8}
Al-5.27a/oZn Reverted and Irradiated	253	1×10^{-6}	2×10^{-5}	

^(a) Vacancy concentration computed by the Meehan-Brinkman analysis, giving the vacancy concentration required for the observed temperature of the resistivity peak.

^(b) Point-defect concentration at the beginning of zone formation as computed from the irradiation-induced resistivity remaining at the start of zone formation.

Since these values are from three to four orders of magnitude larger than the number of primary events that occurred during the irradiation, it is reasonable to suggest that fast-neutron irradiation did not produce any nucleation sites for G.P. zone formation.

9. Irradiation and Solution Hardening (T. J. KOPPENAAAL)

Publications

T. J. Koppenaal, W. C. T. Yeh,[†] and R. M. J. Cotterill, *Lattice Defects in Neutron Irradiated α Cu Solid Solution Alloys*, Phil. Mag. **13**, 867 (1966).

T. J. Koppenaal, *Comments on "The Effect of Fast Neutron Damage on the Deformation of Copper-Tin Alloys,"* Acta Met. **14**, 681 (1966).

T. J. Koppenaal and R. J. Arsenault,[‡] *Some Notes on the Strengthening Mechanism in Neutron Irradiated Copper Single Crystals*, Phys. Stat. Sol. **17**, 27 (1966).

The Dislocation-Defect Interaction for Neutron-Irradiation Strengthening in Copper Single Crystals

The thermally activated slip mechanism in neutron-

irradiated copper single crystals has been investigated with stress-relaxation measurements from 77 to 420°K. Values of $(\partial \ln \dot{\gamma} / \partial \tau^*)_{\tau}$ and $(\partial \tau^* / \partial T)_{\dot{\gamma}}$ can be directly established with this experimental technique ($\dot{\gamma}$ is the strain rate, T the temperature and τ^* the effective stress). The activation enthalpy, H , for slip is then calculated by the expression,

$$H = -kT^2 \left(\frac{\partial \tau^*}{\partial T} \right)_{\dot{\gamma}} \left(\frac{\partial \ln \dot{\gamma}}{\partial \tau^*} \right)_{\tau}, \quad (1)$$

where k is Boltzmann's constant. The results of the $H = H(\tau^*)$ measurements are shown in Figure 288; data previously obtained by Koppenaal and Arsenault⁽⁴³⁵⁾ by creep and tensile measurements are included for comparison purposes. The solid line is the theoretical stress dependence of H from Fleischer's

[†] Michigan Technological University, Houghton, Michigan.

[‡] University of Maryland, College Park, Maryland.

⁽⁴³⁵⁾ Koppenaal, T. J., and Arsenault, R. J., Phil. Mag. **12**, 951 (1965).

45418

FIG. 288. The Effective Stress, τ^* , Dependence of the Activation Enthalpy, H , Calculated by Equation (1). The solid line is Fleischer's theoretical stress dependence.

45422

FIG. 289. H_0 , The Activation Enthalpy at Zero Effective Stress, vs Testing Temperature.

model^(436, 437) for strengthening by tetragonal distortions. A good agreement between experiment and theory is achieved if we use a value of 3.0 eV for H_0 , the activation enthalpy at zero effective stress, as in our previous investigation.⁽⁴³⁵⁾

We may also calculate H_0 directly by the expression,

$$H_0 = -kT \frac{d \ln \dot{\gamma}}{d \left(\left[1 - \left(\frac{\tau^*}{\tau_0^*} \right)^{1/2} \right] \right)}, \quad (2)$$

(436) Fleischer, R. L., *Acta Met.* **10**, 835 (1962)

(437) Fleischer, R. L., *J. Appl. Phys.* **33**, 3504 (1962)

45409

FIG. 290. Experimental Force, F^* , vs Thermally Activated Distance $(\chi - \chi')$ for the Dislocation-defect Interaction Responsible for Neutron Irradiation.

where τ_0^* is τ^* at $T = 0^\circ\text{K}$. The differential in Equation (2) is experimentally determined and values of $H_0 = H_0(T)$ are shown in Figure 289. H_0 is essentially temperature independent. The average value of H_0 is 2.85 eV, which is in good agreement with the value of 3.0 eV determined from Figure 288. The results of Diehl, Seidel and Niemann,⁽⁴³⁸⁾ who use a different model, are also shown in Figure 289 and a temperature dependent H_0 is observed. All of our results, however, indicate that H_0 is temperature independent.

An experimental force-distance curve for the interaction of mobile dislocations with irradiation-produced obstacles is shown in Figure 290. Also included are the theoretical force-distance curves for the Fleischer model and the Mott-Nabarro⁽⁴³⁹⁾ model.

From the results given in Figures 288, 289 and 290, the following conclusions are made:

1. The thermally activated rate controlling mechanism for slip in neutron-irradiated copper single crystals is overcoming the Fleischer interaction.
2. The activation energy for slip at zero effective stress is a unique value, independent of testing temperature. Thus, the effective obstacle size is independent of testing temperature. The exact nature of the obstacles have been described elsewhere.⁽⁴³⁵⁾

(438) Diehl, J., Seidel, G. P., and Niemann, L., *Phys. Stat. Sol.* **11**, 339 (1965).

(439) Mott, N. F., and Nabarro, F. R. N., *Report of Bristol Conf. on Strength of Solids*, (London: The Physical Society) p. 1 (1948).

10. Irradiation Hardening (C. ARNE ARENBERG AND T. H. BLEWITT)

Publication

C. Arne Arenberg and T. H. Blewitt, *Radiation Hardness in Copper Single Crystals*, Bull. Am. Phys. Soc. **11**, 209 (1966) [Abstract].

Studies of the effects of fast neutron bombardments on the yield stress of the fcc metals have continued. The purpose of these studies was to resolve the controversy relating to the dose dependence of the yield stress, i.e., whether the yield stress increases as the dose to the one-third power or whether the increase in yield stress increases as the one-half power of the dose with a saturation term. This controversy can be settled by

are shown in Figure 291. It should be noted that the spread in data is the result of inability to reproduce absolute magnitudes. For any specific run very small deviations are apparent.

2. A natural fit to the one-third power dependence can be seen in Figure 292 where the data from Run No. 10 (bombarded at 4.2°K) are plotted. It is apparent from this figure that the most favorable curve of the form $\Delta\tau = \phi^{1/2}$ requires saturation effects to become appreciable at doses greater than 5×10^{15} , a rather unlikely result.

3. Preliminary data on gold and silver crystals also

FIG. 291. Effect of Neutron Irradiation at 4.2°K on the Yield Point of Soft Copper Single Crystals.

studying at very low temperatures the dose dependence of crystals of low initial yield stress at very low neutron doses. A tensile machine previously described,⁽⁴⁴⁰⁾ was designed to operate in the CP-5 fast flux facility in a bath of liquid helium. It should be noted that the tensile machine has a strain sensitivity of 10^{-6} cm/cm so that micro-yield stresses can be observed. The results can be summarized in the following way:

1. The macro-yield stress [$(\Delta l/l) > 10^{-4}$] of copper crystals irradiated at 4.2°K varies with 0.333 power of the neutron dose for doses ($E > 0.5$ MeV) ranging from 2.5×10^{14} n/cm² (7 min. full power operating time) to 3.6×10^{17} n/cm² (10^4 min. full power operating time). The data have been obtained from 14 different runs of which 7

46225

FIG. 292. Dose Dependence of the CRSS for Copper Single Crystals.

(440) ANL-7155, Annual Report for 1965, Metallurgy Division, p. 266.

45924

FIG. 293. Effect of Neutron Irradiation at 4.2°K on the Micro-yield Stress of Copper.

46223

FIG. 294. Dose Dependence of CRSS for a Prestressed Copper Single Crystal.

show that the macro-yield stress depends on third power of the dose when bombarded at 4.2°K.

4. The micro-yield stress of copper single crystals irradiated at 4.2°K shows a small, if any, increase in the yield stress for doses less than 5×10^{15} . For doses from 5×10^{15} to 5×10^{16} the micro-yield stress increases as the third power of the dose. This can be seen in Figure 293.

5. The fact that the micro-yield stress is much smaller than that of the macro-stress at 4.2°K, whereas they are similar at room temperature according to the data of Koppenaal,⁽⁴⁴¹⁾ suggest some important changes in the structure of the defects occur between 4.2°K and 300°K.

⁽⁴⁴¹⁾ Koppenaal, T. J., *Microstrain Yield Stress in Neutron-Irradiated Copper Single Crystals*, J. Appl. Phys. **35**, 2750 (1964).

FIG. 295. Dose Dependence of the CRSS of a Copper Single Crystal in the Very Low Dose Region.

6. Experiments on prestressed samples show that the yield stress increases less rapidly than unstressed samples until the irradiation-induced stress exceeds that of the prestressed sample. Thereafter the hardening occurs at the same rate as in unstressed samples. (See Figure 294.) This clearly suggests work hardening is not simply additive to irradiation hardening; a serious question is raised as to the validity of the $\Delta\tau$ method of interpreting the data. On the other hand a model, if one assumes that the yield stress varies inversely with the barrier distance, would suggest that $\tau_{\text{irrad}} = (\tau_{\text{total}}^3 - \tau_{\text{prestress}}^3)^{1/3}$. This shows the one-third power dependence.
7. Experiments at doses between 7×10^{12} and 4×10^{13} show that the change in yield stress $\Delta\tau$ is not proportional to the dose to the half power. On the other hand, τ_{irrad} determined from the cube root of the difference between τ_{meas}^3 and τ_0^3 shows a direct proportionality to the one-third power of the dose. This can be seen in Figure 295.
8. Annealing experiments show that less than 1% recovery occurs between 4.2°K and 100°K. Experiments were performed by pulse annealing, and yield stress was measured at the pulse temperature as well as the reference. Verification of the sample temperature was thus obtained from the temperature dependence of the yield stress. This is illustrated in Figure 296.

These results verify that the macro-yield stress varies the third power of the neutron dose. The data of the micro-yield stress clearly show that the hardening is friction-type hardening and suggest that dislocations are able to move below the macro-yield stress. A model

FIG. 296. Isochronal Annealing of Copper.

would then suggest that the dislocations move and become entangled in barriers. As the stress increases dislocations are apparently able to bypass some barriers but are not able to sweep through the entire barrier field until the yield stress is reached. Apparently pileups are generated when stresses intermediate to the micro- and macro-yield stress occur. The stress on the leading dislocation will thus be given by

$$\tau' = g\tau = n\tau$$

where τ is the applied stress; g is the stress raiser; n is the number of dislocations in the pileup.

If it is assumed that the dislocations bypass the barriers by bowing out of the dislocations between the

barriers, then $\tau \propto 1/l$ where l is the distance between barriers. On the other hand the number of irradiation-induced barriers on the slip plane increases as the half power of the dose. It can be concluded for this model that

$$\tau' \propto \phi^{1/2}.$$

From this and the fact that the applied stress increases as the third power of the dose, the number of dislocations in a pileup must increase as the half power of the applied stress so that

$$\tau' \propto \tau^{3/2} \text{ and } \tau \propto \phi^{1/3}.$$

Carrying this model one step further the influence of the critical shear stress can be deduced. Assume that in an unirradiated crystal, barriers to the motion of dislocation lines determine the yield stress. Neutron irradiation will then add more barriers and the critical

shear stress will be determined by the sum of the barriers, *i.e.* $\tau \propto (n_{\text{irrad}} + n_0)^{1/2}$. Since $n_{\text{irrad}}^{1/2} \propto \tau_{\text{irrad}}$ and $n_0^{1/2} \propto \tau_0$

$$(\tau')^2 = (\tau_0')^2 + (\tau_{\text{irrad}}')^2.$$

However dislocation pileups will result and as noted before:

$$(\tau')^2 \propto \tau_{\text{meas}}^3; \quad (\tau_0')^2 \propto \tau_0^3; \quad (\tau_{\text{irrad}}')^2 \propto \tau_{\text{irrad}}^3$$

so that

$$\tau_{\text{irrad}} = (\tau_{\text{meas}}^3 - \tau_0^3)^{1/3}.$$

The data in Figures 294 and 295 analyzed in accordance with the previously mentioned model show that the dose dependence of the CRSS extrapolates from higher dose data and is some indication of the validity of the model.

K. CORROSION RESEARCH

1. Low-Pressure Oxidation and Growth Morphology

(R. K. HART, J. K. MAURIN AND D. G. PILNEY)

Publications

- W. E. Ruther, R. R., Schlueter, R. H. Lee and R. K. Hart, *Corrosion Behavior of Steels and Nickel Alloys in Superheated Steam*, Corrosion, **22**, 147 (1966).
- R. K. Hart and D. G. Pilney, "A Compact Vacuum—Path 20 Scanner," in *The Electron Microprobe*, p.472, John Wiley and Sons, Inc., New York (1966).
- R. K. Hart, *An Investigation of Composite Aluminum-Nickel Evaporated Films*, J. Appl. Phys., **37**, 2918 (1966).
- R. K. Hart, *Electron Diffraction Techniques and Their Applications to the Study of Surface Structure*, Prog. Nucl. Energy, Series IX, **7**, 1, (1966).
- R. K. Hart and J. K. Maurin, "Growth of Oxide Nuclei on Iron," Proceedings of *Sixth International Congress for Electron Microscopy*, Kyoto, Vol. 1, 539 (1966), Maruzen Ltd., Tokyo, Japan.
- R. K. Hart, T. F. Kassner and J. K. Maurin, "Residual Gas Analysis in an Auxiliary Pumped Siemens Electron Microscope," Proceedings of *Sixth International Congress for Electron Microscopy*, Kyoto, Vol. 1, 161 (1966), Maruzen Ltd., Tokyo, Japan.

a. THE GROWTH OF OXIDE NUCLEI ON METAL FOILS

In last year's annual report (ANL-7155, p. 280) an "induction period" was described, during which no observable oxide nuclei grew on aluminum in the low-pressure residual gas in the electron microscope. As a first step to understanding this phenomenon, additional observations have been made.

Although the 1:4 perchloric acid-ethyl alcohol electrothinning solution appears to work very well on iron, it has not been found entirely suitable for aluminum. The most suitable preparation technique for aluminum appears to require the use of 6 v/o of concentrated (70 w/o) perchloric acid in methanol, the electrolyte being kept at -72°C during thinning. The sample must be rinsed immediately after thinning in a large volume (~ 600 ml) of methanol at 72°C , then processed through three successive rinses in methanol at room temperature before cutting and mounting for the electron microscope. This electrolyte, which was developed by Hopkins, Peterson and Baker⁽⁴⁴²⁾ has

⁽⁴⁴²⁾ Hopkins, E. N., Peterson, D. T., and Baker, H. H., *A Universal Electropolishing Method*, 19th AEC Metallography Group Meeting, April 20-22, 1965, Oak Ridge, Tennessee.

also been used successfully to thin iron, cobalt, stainless steel (304), beryllium and titanium.

Aluminum thinned in the 6% perchloric acid electrolyte, when examined electron optically, appears to carry very little polishing film and the surface appears smooth and free of polishing artifacts such as "orange-peel" microroughness.

As can be expected, the thinning process has an important bearing on the formation of nuclei. Nuclei grown on aluminum surfaces thinned in 1:4 perchloric acid-ethyl alcohol often looked polycrystalline as is shown in Figure 297. These nuclei appeared to be made up of aggregates of smaller particles. Their polycrystalline nature was confirmed by electron diffraction. On the other hand, cold 6% perchloric acid electrolyte produced surfaces that yielded the type of nuclei shown in Figure 298. Diffraction patterns of selected areas showed these nuclei to be highly crystallized (spot patterns) and to be epitaxially related to the underlying metal.

Changes in the electrothinning method do not appear to substantially alter the induction time required for nuclei to form (Table 102). Data obtained on growth kinetics of nuclei have been more reproducible from specimens that were thinned in 6% perchloric acid-methanol. The induction time, ⁽⁴⁴³⁾ T_N , for nuclei to appear has been investigated for a wide variation of experimental conditions, and the results to date are given in Table 102. With the exception of observations made at regular microscope pressures, the data show that no great change in T_N occurs when the pressure is varied over several orders of magnitude. Work in process on the oxygenated series indicates that there may be a substantial reduction in T_N when higher-oxygen partial pressures are used. The short induction period under regular microscope vacuum conditions could be entirely due to the higher reaction temperature used in this series.

A detailed investigation of this induction phenomenon will commence as soon as a vacuum electro-microbalance can be put in operation.

More data have been obtained on the number of nuclei/cm² formed on (001) and (110) aluminum sur-

⁽⁴⁴³⁾ Gwathmey, A. T., Leidheiser, H., and Smith, G. P., *Influence of Crystal Plane and Surrounding Atmosphere on Chemical Activities of Single Crystals of Metals*, NACA TN No. 1460, June 1948.

105219 80,000×
Fig. 297. Oxidized Aluminum Foil, Which Had Been Thinned in 1:4 Perchloric Acid/Ethanol, Showing a Nucleus Consisting of Aggregates of Smaller Particles.

107191 70,000×
Fig. 298. Oxidized Aluminum Foil, Which Had Been Thinned in 6% Perchloric Acid/Methanol at -72°C , Showing Highly Crystallized Nuclei.

TABLE 102. VARIATION OF INDUCTION PERIOD (T_N) WITH TEMPERATURE, PRESSURE, AND SURFACE PREPARATION

	Microscope Vacuum	Microscope Vac. + Cold Shield		Auxiliary Vacuum System			Auxiliary Pumped and then Oxygenated			
Run Number	№ 1-№ 13	№ 21	№ 22	№ 18	№ 19	№ 23	№ 24	№ 25	№ 26	№ 27
Base Pressure (Torr)	1×10^{-5}	1×10^{-6}	7×10^{-7}	6×10^{-8}	4×10^{-8}	6×10^{-8}	6×10^{-8}	6×10^{-8}	5×10^{-8}	8×10^{-8}
Run Pressure (Torr)							2.5×10^{-7}	7×10^{-7}	1×10^{-6}	5×10^{-6}
Temperature ($^{\circ}\text{C}$)	540	440	440	440	440	440	440	440	440	440
Surface Preparation ^(a)	(1)	(2)	(2)	(1)	(1)	(2)	(2)	(2)	(2)	(2)
Surface Orientation	(001) and (110)	(110)	(110)	(001)	(110)	(110)	(110)	(110)	(001)	(110)
T_N (min)	<4	9	6	8	8	11	8	9	9	8 ^(b)

^(a) (1)—1:4 perchloric acid-ethyl alcohol at 10°C . (2)—6% perchloric acid-methyl alcohol at -72°C .

^(b) Nuclei visible in grain boundary at $T_N = 3$ min, but did not appear in grains until $T_N = 8$ min.

TABLE 103. NUCLEI/CM² FORMED ON ALUMINUM SURFACES IN ELECTRON MICROSCOPE RESIDUAL GASES—DATA THROUGH RUN № 22

Crystal Face	Microscope Vacuum 1×10^{-6} Torr and 540°C	Microscope Vacuum plus Cold Shield 7×10^{-7} Torr and 440°C	Auxiliary Vacuum System 5×10^{-8} Torr and 440°C
(001)	2.7 ± 0.8 (11) ^(a)	1.3 ± 0.4 (6)	1.9 ± 0.5 (5)
(110)	2.7 ± 1.6 (11)	1.2 ± 0.3 (13)	4.8 ± 1.0 (5)

^(a) Number of counts used to determine standard deviation.

faces. The area on each micrograph over which counts were made was equivalent to $80 \mu^2$ of surface on the specimen. These data are given in Table 103 and they

indicate that there is not a substantial difference in nuclei formation on (001) and (110) aluminum under the conditions of experiment. This agrees with the oxidation work of Gwathmey et al.⁽⁴⁴³⁾ who observed that the oxidation rates about (001) and (110) aluminum surfaces were comparable (qualitatively) and higher than that about (111) aluminum.

Improvements have been made in the operating conditions of the electron microscope used for these nucleation experiments. This instrument can now be routinely operated with the pressure in the specimen chamber 5×10^{-8} Torr or less. This has mainly resulted from the use of a redesigned cooling ring, which is kept at liquid-nitrogen temperature during operation of the microscope.

The pressures that can be obtained in the microscope under different operating conditions, together with

TABLE 104. RESIDUAL GAS ANALYSIS IN SIEMENS ELECTRON MICROSCOPE

Component	Mass No.	Regular Microscope Run # 18	Regular Microscope Plus Cold Shield Run # 19	Regular Microscope Plus Cold Shield—Plus Auxiliary System Run # 20
Methane	16	8.87×10^{-9} torr	1.79×10^{-9} torr	2.56×10^{-10} torr
Ammonia	17	5.00×10^{-8}	8.45×10^{-10}	2.26×10^{-10}
Water	18	7.65×10^{-6}	2.07×10^{-8}	5.30×10^{-9}
Neon	20	4.61×10^{-8}	6.95×10^{-10}	2.50×10^{-10}
Ethane	28	1.29×10^{-8}	1.87×10^{-9}	1.86×10^{-10}
Nitrogen	28	7.52×10^{-7}	4.49×10^{-7}	2.12×10^{-8}
Carbon Monoxide	28	9.57×10^{-7}	—	—
Biethyl Ether	31	4.62×10^{-9}	1.49×10^{-10}	2.64×10^{-11}
Oxygen	32	2.67×10^{-7}	1.46×10^{-7}	8.61×10^{-9}
Argon	40	2.00×10^{-8}	9.75×10^{-8}	5.12×10^{-10}
Butene-1	41	4.80×10^{-8}	4.48×10^{-10}	1.14×10^{-10}
2-2 DM-Butane	43	7.28×10^{-8}	9.94×10^{-10}	2.93×10^{-10}
Acetone	43	8.20×10^{-9}	1.49×10^{-10}	2.40×10^{-11}
Carbon Dioxide	44	6.30×10^{-8}	1.68×10^{-8}	2.87×10^{-9}
Pentene-2	55	3.92×10^{-8}	5.65×10^{-10}	1.57×10^{-10}
Total Pressure	Torr	1.0×10^{-5}	6.5×10^{-7}	4.0×10^{-8}
ΣP_{CH} , Torr		1.94×10^{-7}	5.97×10^{-9}	1.06×10^{-9}
$\Sigma P_{CH}/P$ Total		0.019	0.0092	0.0264
Contamination Rate (Average) Å/min.		48	44	43

the partial pressures of constituent gases are given in Table 104. Under the best vacuum conditions cited and the specimen above 400°C contamination of the specimen is negligible. However, in high-resolution microscopy of the specimen after it has cooled to room temperature, the contamination rate at 5×10^{-8} Torr is not very different from that observed under regular microscope vacuum. Measurements of the contamina-

tion rate in over twenty runs have varied from several angstroms per minute to about sixty. Although this is a wide variation, it is not as objectionable as has been reported in the literature for conventionally pumped electron microscopes. In such cases, rates between 200 and 500 Å per minute are not uncommon.⁽⁴⁴⁴⁾

⁽⁴⁴⁴⁾ Hartman, R. E., and Hartman, R. S., Laboratory Investigation, **14**, 409 (1965).

2. Mechanism of Zirconium Oxidation (J. LEVITAN, J. E. DRALEY, R. H. SPITZER, AND C. J. VAN DRUNEN)

a. ELECTRICAL POTENTIALS ACROSS GROWING FILMS OF REACTION PRODUCTS

Potentials have now been measured across the film forming on zirconium in a number of gases. A number of interesting observations can be made.

Oxygen: At 700°C, the potential reaches values up to -1.3 volts. The value observed depends somewhat on experimental conditions, but -1.3 is the number typical of "good" measurements in oxygen at one atmosphere pressure.

The potential is generated by the transport of electrons and (oxygen) ions through the oxide film at rates such that the rates of transfer of electric charge in opposite directions are equal. Thus the magnitude and

sign of the potential depend on the relative ease of transport of ions and electrons. These transport processes in turn depend on the oxide defect structure. Since the defect structure can be expected to depend upon the pressure of environmental oxygen, at least over some pressure range, the potential can be expected to depend on oxygen pressure.

Potentials were recorded during oxidation of zirconium, with the oxygen pressure changed periodically. The experimental setup was similar to one described previously.⁽⁴⁴⁵⁾ Results for 700°C are presented in Figure 299. Potentials were nearly independent of oxygen pressure (p_{O_2}) in the range 1 to 400 mm Hg.

⁽⁴⁴⁵⁾ Bradhurst, D. H., Draley, J. E., Van Drunen, C. J., J. Electrochem. Soc., **112**, 1171 (1965).

106-9333

FIG. 299. Potential Dependence upon Oxygen Partial Pressure at 700°C.

Below 1 mm, potentials were lower, decreasing with decreasing oxygen pressure.

Zirconium oxidation is known to be independent of p_{O_2} in the 1 to 400 mm range. Thus the unchanging potential corresponds to an unchanging oxidation rate with changing p_{O_2} . Results shown in Figure 299 can be considered as an indicator of a difference in kinetic behavior at lower pressures. This has been confirmed experimentally (see later).

Nitrogen: No potential was observed during the nitriding of zirconium at $p_{N_2} = 100$ mm (700°C). The resistance of the film formed during the reaction, determined by applying small currents to the samples, was lower by 2 orders of magnitude than that of an equivalent forming oxide film. Admission of 2–3 mm oxygen to the N_2 system caused an immediate rise of the potential (to $-1.08V$) and resistance (from 10^3 to $\sim 10^5 \Omega$). The potential and resistance then gradually declined. The phenomena can be explained by formation of ZrO_2 from ZrN :

The zirconia may uniformly cover the exterior surface of the ZrN or oxygen might diffuse through the porous nitride to the metal surface and form a thin ZrO_{2-s} film. The observed decay in potential and resistance suggests that the oxide diffuses into the nitride to form a "mixed" film, with oxygen and nitrogen incorporated into the crystal lattice.

Carbon Dioxide: ZrO_2 is the predominant product of the oxidation of zirconium in CO_2 :

Small amounts of carbon are also found in the oxide. In CO_2 , a potential of only 20 to 30 mV (negative) was recorded. Admission of small amounts of oxygen caused a rise in potential to values corresponding to that observed during oxidation in oxygen. This indicates that oxygen reacted with the previously formed oxide. The resistance of the film formed in CO_2 was also found to be lower than that of typical films formed in O_2 .

Water Vapor: When the oxidizing atmosphere consisted of argon saturated (at 28°C) with water vapor, electrical parameters were similar to those observed in CO_2 ; presumably a similar explanation is valid.

It can be concluded that a high potential and resistance are specific for oxidation of zirconium by oxygen. Additional electrical measurements can probably be used to elucidate the differences between films and between reaction mechanisms in these environments.

b. OXIDATION AT NORMAL PRESSURE

A new kinetic model for the oxidation of zirconium has been developed, based on the known facts. According to Pemsler,⁽⁴⁴⁶⁾ the early rate of oxidation and the rate of oxygen diffusion into the metal depend on the orientation of the metal exposed. The amount of oxy-

(446) Pemsler, J. P., J. Electrochem. Soc., **105**, 315 (1958).

gen diffused varies with the square root of time ($= \sqrt{2kt}$). At longer exposure times, the rate of oxidation varies as $t^{-1/2}$, or approximately as (oxide thickness) $^{-1}$. Also at the longer times, the thickness of the total oxide film is approximately uniform across the surface of polycrystalline metal. At short exposure times the tetragonal modification of ZrO_2 is the predominant oxidation product, while at longer times the monoclinic ZrO_2 predominates.

It is proposed that the primary product of oxidation is always the tetragonal oxide (thickness at any time $= x$), and that when its thickness on any metal grain reaches the invariant value s the entire thickness is instantly transformed into monoclinic oxide. During the next growth cycle, the oxidation rate is controlled by the combination of the (constant thickness) monoclinic oxide and the growing tetragonal oxide. If the parabolic growth constant for tetragonal oxide is b and that for the monoclinic oxide is c , the rate of growth of tetragonal oxide on one grain during the i th growth cycle is given by:

$$\frac{dx}{dt} = \frac{b}{x + \frac{b}{c}(i-1)s} - \frac{\sqrt{k/2}}{\sqrt{t}}$$

The total rate of weight gain is given by:

$$\frac{dw}{dt} = \frac{b}{w - \left(1 + \frac{b}{c}\right)(i-1)s - \sqrt{2kt}},$$

where w is the weight gain per unit area on the grain.

Using these equations, weight gain curves have been constructed for a number of grains. When the constants had the following values: $k = 3.816 \alpha$ ($\text{mg}^2, \text{dm}^{-4}, \text{min}^{-1}$), $b = 76.31 \alpha$ ($\text{mg}^2, \text{dm}^{-4}, \text{min}^{-1}$), $c = 19.08$ ($\text{mg}^2, \text{dm}^{-4}, \text{min}^{-1}$), $s = 77.52$ ($\text{mg}, \text{dm}^{-2}$); the first two growth cycles had the appearance shown in Figure 300. The multiplier α is used to adjust the values of k and b for orientation of particular metal grains.

These four curves were averaged to produce the hypothetical weight gain curve for a polycrystalline specimen shown in Figure 301. For long times oxidation is parabolic, in accord with experiment. For shorter times, irregularity is observed. This can be examined more closely on the log-log plot of Figure 302, where results of one experiment are compared with those calculated. The fit is excellent: both the experimental and theoretical curves are parabolic (slope $= 1/2$) up to some time (16.4 minutes for the theoretical), then become approximately cubic. The experiment was terminated at 300 minutes; that is about the time the theoretical curve starts to bend upward on the log-log plot.

The model requires that the amount of tetragonal oxide on one oxidizing specimen remain approximately constant with time, as the amount of monoclinic oxide increases. Preliminary X-ray reflection diffractograms (at temperature) show the continuing existence of tetragonal oxide and increasing amounts of the monoclinic oxide. It is not yet possible to state how the amount of tetragonal oxide varies with time.

The theory predicts that single crystal faces should

FIG. 300. Weight Gain Curves for Four Grains.

46768

FIG. 301. Parabolic Plot for Calculated Average Curve (Long Time).

46767

FIG. 302. Comparison of Calculated and Experimental Oxidation of Zirconium at 700°C.

show weight gains like those in Figure 300; data are not available. Material with preferred orientation should exhibit different oxidation kinetics during the "sensitive" time; such variations in kinetics have been observed.

The results of the theoretical analysis are very encouraging. More careful fitting should be done, and predictions about single crystal faces should be confirmed. In addition, measurements of oxygen diffusion rates and initial parabolic oxidation rates for individual grain faces should be completed. This will allow essentially complete confirmation of the model.

Oxidation at Low Pressures

Changes in electric field occurring at low p_{O_2} (see earlier section) indicate changing conditions on the solid-gas interface and consequently a difference in oxidation kinetics. The Ainsworth balance system was modified for (low) constant pressure measurements by employing a Granville-Phillips automatic control valve.

The results of a number of low pressure oxidation experiments at 700°C are presented in Figure 303. It is evident that the rate of weight gain is a function of oxygen pressure in the 10^{-3} mm range. Such experiments

FIG. 303. Low-Pressure Oxidation of Zirconium at 700°C.

6770

show maximum deviation from high-pressure behavior at early times, as indicated by comparison with the curve for oxidation in oxygen at 1 mm pressure. At longer exposure times the oxide films formed at the lower pressures become thick enough to be substantially protective, and it appears that oxidation behavior is approaching that typical of normal-pressure oxidation. Similar results were obtained at 550 and 800°C.

At the shorter exposure times, typical behavior is represented schematically in Figure 304. Different stages can be described as follows:

Stage I. This is when the first measurable weight gain occurs. This stage is clearly distinguishable at 800°, difficult to identify at 700° and not observed at 500°C. Weight gains are small enough so that the curve shape has not been determined reliably. It is clear, however, that Stage II does not extrapolate to the origin and there is a transition from Stage I to Stage II (at 800°C the time at transition is about 20–40 minutes for the pressures used). Usually it has appeared that the average rate in Stage I is greater than that in Stage II.

Stage II. Oxidation occurs at a constant rate for all runs at 700 and 800°C. The oxidation rate is observed to be approximately proportional to the gas pressure, over the range 2 to 7×10^{-3} mm (at 700°).

Stage III. At the end of Stage II an increase in rate is observed, followed by a period when the rate again remains constant. Again the rate of weight gain is approximately proportional to the absolute pressure.

Stage IV. A time is reached when the growing oxide

106-9346 Rev. 1

FIG. 304. Schematic Presentation of Low Pressure Zirconium Oxidation.

film significantly limits the reaction rate. This leads to a continuously decreasing rate. At first, the change in reaction rate is not very rapid, but when the oxide film essentially completely determines the rate a curve somewhere between cubic and parabolic is observed.

A typical weight-gain curve is given in Figure 305, for oxidation at 700°C. The essential features can readily be observed.

It probably will not be possible to explain the various stages in the reaction until more information is available. Perhaps in Stage I there is no oxide film at all, and oxygen diffuses into the metal. It is not known at what time an oxide film first covers the surface and it

46765

FIG. 305. Typical Low Pressure Zirconium Oxidation at 700°C.

is not known whether the early oxide film has an influence on reaction rate.

It will be necessary to explain the increase in linear rate constant occurring between Stages II and III. For a considerable number of specimens, transition from

Stage II to III (and also from Stage III to IV) has occurred at reproducible weight gains. This suggests that some specific physical change occurs at the transition times. Further speculation does not appear valuable at this time.

3. Polarization Studies (R. A. LEGAULT AND W. J. BETTIN)

The expression for the change in solution potential of 1100 aluminum (in high-purity water) associated with small applied currents has been revised to take into consideration potential changes at three locations: (1) the oxide-solution interface, (2) across the oxide film, and (3) the metal-oxide interface.

At the oxide-solution interface the reaction occurring is the reduction of water to form gaseous hydrogen (and hydroxide ion). The expression for the change in potential there is

$$-\Delta E_s = K_s \ln (1 + \Delta i_e / i_e), \quad (1)$$

where K_s is the electrochemical constant for hydrogen liberation ($RT/\alpha zF$ in the conventional electrochemical rate expression), i_e is the electron current through the oxide before polarization and Δi_e is the change in this quantity caused by the passage of an applied cathodic current. In the expression for K_s , R is the gas constant, T is the absolute temperature, F is Faraday, z the number of electrons produced or consumed per unit

reaction and α the transfer coefficient, which indicates the fraction of the total electrode potential that drives the forward reaction.⁽⁴⁴⁷⁾

Through the oxide film three charged particles pass: aluminum ions (outward), protons (inward) and electrons (outward). With each there is an associated current, and a change in current during polarization. It is assumed that for small applied currents the changes in current are ohmic; i.e. there is an effective resistance for each. Thus

$$\begin{aligned} -\Delta E_f &= \Delta i_e R_e \\ &= \Delta i_H R_H \\ &= -\Delta i_a R_a \end{aligned} \quad (2)$$

The applied current,

$$I = \Delta i_e + \Delta i_H - \Delta i_a. \quad (3)$$

⁽⁴⁴⁷⁾ Hampel, C. A., pp. 1135-1137 in *The Encyclopedia of Electrochemistry*, Reinhold Publishing Corp., New York, 1964.

When C is the resistance of the parallel array of the three resistances, Equations (2) and (3) can be combined to:

$$-\Delta E_f = IC \quad (4)$$

At the metal-oxide interface two electrochemical reactions occur: the reduction of protons to produce hydrogen and the oxidation of aluminum. The following expressions can be written:

$$-\Delta E_M = K_H \ln (1 + \Delta i_H / i_H) \quad (5)$$

$$\Delta E_M = K_a \ln (1 + \Delta i_a / i_k) \quad (6)$$

In Equation (6), i_k is the corrosion current (equal to the anodic or aluminum ion current before polarization).

The change in potential for the entire complex reaction is then given as the sum of the three potential changes (Equations 1, 4 and 6), when Equations (2) and (3) are used to eliminate Δi_e and Δi_a :

$$-\Delta E = K_s \ln (1 + IC / i_e R_e) + IC - K_a \ln (1 - IC / i_k R_a) \quad (7)$$

If R_a is large with respect to R_e and R_H , or C / R_a is small, the last term in Equation (7) can be approximated well by the first term of the series expression for the logarithm. Then:

$$-\Delta E = K_s \ln (1 + IC / i_e R_e) + IC + K_a IC / i_k R_a \quad (8)$$

Combining the constants, so that $C / i_e R_e = D$, and $C(K_a / i_k R_a + 1) = R$ provides the final expression:

$$-\Delta E = IR = K_s \ln (1 + ID). \quad (9)$$

Considerable effort has been applied to fitting this equation to polarization data for 1100 aluminum in high-purity water at 97°C. Since K_s is the electrochemical constant for the liberation of hydrogen into the solution, its value should be independent of exposure time. For a number of solutions, the value of α (see note after Equation (1)) has been determined to be close to 0.5. With this value, the value of K_s for the test condition should be 63.8. By selecting optimum values of the other two constants, excellent fits to the data are obtained, as illustrated in Figure 306. The circles are data points; the lines are calculated from Equation (9). Numbers in parentheses are the hours of exposure of the specimen to the water at the times the polarization measurements were made.

The slope of the polarization curves at $I = 0$, designated the polarization resistance (P), can be calculated from

$$P = \left(\frac{d(-\Delta E)}{dI} \right)_{I=0} = R + K_s D \quad (10)$$

The values of P calculated from the constants used for the curves in Figure 306 agree quite well with the experimental slopes calculated from very small current polarization. The values of D also vary with time in a fashion that seems quite reasonable in view of the variation of corrosion rate and of P (experimental) with time. Values of D changed only slightly with exposure time.

The equation that has been derived has provided excellent agreement with experimental data and the authors have considerable confidence that the form of the equation is correct. It must be noted, however, that

Fig. 306. Polarization of 1100 Aluminum in High Purity Water at 97°C.

agreement can be achieved with other values of the three constants in the equation, and unequivocal values for these constants are necessary if we are to extract meaningful information concerning the mechanisms involved.

The determination of unequivocal values for these constants was approached in two ways:

- (1) attempts to refine the apparatus in order to obtain more precise data, and
- (2) computer searching for error minima based on various criteria in an effort to narrow the ranges within which the values of the constants are known.

Apparatus

The polarization measurements involve photographing the potential-decay curves (measured on an oscilloscope screen) that result when the polarizing current is turned off. The ohmic contribution to the over-potential, which reflects the high resistivity of the test water, decays virtually instantaneously, whereas the contributions of interest, which make up only a small portion of the total over-potential, decay in times of the order of one second. This difference in the rate of potential decay makes possible a resolution of the two contributions. Achieving a reasonable degree of precision in the measurement of the smaller contribution requires that as much of the oscilloscope screen as possible be used to

display this portion of the decay curve. It follows that the oscilloscope will be subjected to signals that are very much larger than can be displayed and the consequent overloading of the oscilloscope amplifier could result in distortion of the portion of the decay curve one wished to measure. In an effort to avoid overloading the oscilloscope amplifier, a switch has been used to short out the oscilloscope whenever a polarizing current is impressed. The data just presented were obtained with such a switch incorporated into the measuring circuit. The switch timing is extremely critical and does introduce some uncertainty in the measurement. Ways to solve this problem have been sought that do not require such critical timing. Since none of the many changes in apparatus that were tested has produced any appreciable improvement the conclusion seems unavoidable that the apparatus currently in use is as good as can be achieved without resorting to an elaborate electronics research program.

Computer Searching

The first attempts to evaluate the constants in our polarization equation involved finding the minimum in the sum of the squares of the errors in a series of determinations at different values of polarizing current. The error is defined as $(\Delta E + IR + K_s \ln(1 + ID))$. See Equation (9). Minima were found; but the value of K_s , which the model requires to remain constant with time, could not be determined within a range smaller than several orders of magnitude.

Approximately the same percentage errors (experimental) can be expected at the higher values of impressed current as at the lower ones and hence the criterion of the sum of the squares of the errors attributes a disproportionate amount of importance to the larger errors found at the higher current values. For this reason it was decided to search for the minimum in the sum of the squares of the relative errors, defined as $(\text{Error in } \Delta E)/\Delta E$. A significant improvement was realized as a result of the change in the error criterion but the value of K_s still could not be determined within a range of much less than one order of magnitude. The use of squares in this criterion serves the purpose of keeping the mathematical signs of the errors positive, but it also weights most heavily those data points that are most in error. In order to avoid this sort of disproportionate weighting, the minimum in the sum of the absolute relative errors was sought. Again some improvement was realized but the results were still inadequate.

A series of polarization curves are obtained on each sample at different exposure times. A series of data points measured at different values of impressed current are obtained at each exposure time, and the error cal-

TABLE 105. OPTIMUM CONSTANTS FOR THREE TYPICAL RUNS

Run No.	Time (hours)	P	K	D	R
10	24.3	13.705	84.670	0.056	9.006
	49.6	26.094	84.670	0.286	1.912
	120.4	52.294	84.670	0.600	1.526
	144.6	58.609	84.670	0.669	1.927
	169.2	64.730	84.670	0.753	0.997
	192.4	60.563	84.670	0.705	0.833
	217.7	63.409	84.670	0.740	0.781
	289.8	53.790	84.670	0.627	0.677
	385.7	54.679	84.670	0.643	0.234
12	22.5	20.165	103.81	0.162	3.398
	46.1	26.787	103.81	0.230	2.919
	70.5	38.662	103.81	0.359	1.356
	94.1	40.090	103.81	0.378	0.843
	166.1	53.664	103.81	0.537	-2.078
	213.9	57.254	103.81	0.571	-2.014
	261.8	63.785	103.81	0.651	-3.764
14	46.2	31.823	106.75	0.283	1.639
	70.6	35.276	106.75	0.321	1.025
	142.4	48.037	106.75	0.450	0.034
	191.6	44.908	106.75	0.440	-2.021
	215.3	49.397	106.75	0.489	-2.795
	311.6	73.683	106.75	0.726	-3.806
	360.5	63.954	106.75	0.634	-3.674
	408.2	63.084	106.75	0.619	-3.001

culated for each point. The sum of the absolute relative errors referred to above is the sum of the errors calculated for any series of points at a particular exposure time. Since K_s should be constant for one specimen for the entire exposure period, only R and D were allowed to change with time. All of the sums of the absolute relative errors obtained on a single sample at the various exposure times were then added together and a minimum in this sum of sums was sought. Typical results for the values of constants obtained in this fashion are shown in Table 105.

Results in Table 105 show that the determination of constants still leaves something to be desired. For a number of runs, the range within which K_s is known goes from a value of approximately 60 to one of approximately 120. Some values of R are negative; a result

which is incompatible with the model on which the derivation of the equation was based. This difficulty should disappear with a more accurate knowledge of the value of K_s . It should be noted that arbitrarily setting the value of α at 0.5 and thus setting the value of K_s at 63.8 led to good (but not optimum) fits for all of our experimental data, and all values of R were positive.

The conclusions drawn from attempts to evaluate the experimental data are as follows:

- (1) The derived equation appears to provide a reasonable approximation of the polarization behavior;
- (2) The data obtained in polarization curves is not sufficient to allow us to determine precise values for the constants in the equation;
- (3) An independent determination of one or more of the constants must be obtained.

4. Mechanism of Aqueous Corrosion of 1100 Aluminum (J. E. DRALEY AND R. E. LOESS)

Publication

ANL-6236, *Crevice-Galvanic Corrosion of Aluminum*, by S. Mori, J. E. Draley and R. E. Loess, June 1966.

After an initial period, the amount of corrosion of 1100 aluminum in distilled water at 70°C varies as the logarithm of time. According to a model of the corrosion process previously developed, the primary film of corrosion product oxide cracks when, at each local site on the surface, its thickness reaches a limiting value. The corrosion rate constant should depend upon the rate constant for the growth of the primary film and on the rate constant for penetration of the cracked or secondary product. From corrosion data alone it has not been possible to determine the parameters basic to the model (the two rate constants and the limiting thickness).

An important cause of the cracking of the primary film is believed to be the liberation of hydrogen beneath it. In this case, the growth kinetics of the primary film should be obtainable by determining corrosion-rate constants for specimens held at several potentials where hydrogen evolution does not occur, and extrapolating to the normal corrosion potential.

Accordingly, corrosion tests are being run in which specimen potentials are maintained constant relative to a reference electrode (Ag/AgCl) by means of an interrupter-type potentiostat. Results to date are shown in Figure 307. It can be observed that the trend is for decreasing slopes (rate constants) with

more positive potentials. The "standard" unpolarized specimen maintained a solution potential close to -0.80 V after the first few days. The "intercepts" of the curves also consistently decreased with more positive potential, with the -1.00 V specimen an exception. Cathodic current was required to maintain this potential after the first few days, but apparently the anodic current prevented the "normal" buildup of corrosion product during that initial period.

Unaccountably, there are upward breaks in the curves for the least negative specimens. Experimental difficulties are suspected.

The trend in corrosion rates with potential is as anticipated in the potential region where hydrogen is liberated. As the rate of hydrogen evolution is decreased by the application of more positive potentials, the rate of cracking of the primary film is decreased. This allows the development of thicker, more protective, primary film and the corrosion rate decreases.

A few single crystals of "pure" aluminum have been corroded with the hope that the absence of strong local cathodes, and the absence of grain boundaries would lead to substantially less cracking of the corrosion-product film. It might then be expected that significant periods of growth of the primary film would occur, and that the rate constant could be determined. In all cases, corrosion rate constants were substantially higher than observed for 1100 aluminum.

6769

Fig. 307. Controlled Potential Corrosion Curves 1100 Aluminum- O_2 -Saturated H_2O at $70^\circ C$.

5. High-Temperature Corrosion of Aluminum Alloys (J. E. DRALEY)

This program has now been terminated except for publication of the results. A model for corrosion of alloys containing about 1w/oNi in water at $260^\circ C$ was tested by fitting data from refreshed autoclave tests to the "parabolic" equation. Based on short-time observations, the growth of protective film is parabolic. By analogy with low-temperature observations, dissolution of corrosion product in refreshed systems can be expected to occur at a constant rate after an initial period in which dissolution is more rapid.

The rate equation for the change in the amount of

corrosion product x , is

$$\frac{dx}{dt} = \frac{k_p}{x - ft - g}, \quad (1)$$

where k_p is the parabolic growth rate constant, f is the dissolution rate, and g is the intercept of the dissolution vs. time curve. Integrating yields

$$x = x_0 + \frac{k}{f} \ln \frac{x_0 - g - k/f}{x - ft - g - k/f},$$

where x_0 is the amount of corrosion at $t = 0$. (The rate expression cannot hold at extremely short times, for the amount of product dissolved at $t = 0$ cannot be the significant quantity g .)

Data for four specimens were fitted by minimizing the sums of the absolute errors. The resultant values of the parameters are shown in Table 106. The growth rate constant is seen to be relatively reproducible, whereas there was greater variation in dissolution rate from specimen to specimen.

This had the effect of causing rather poor reproducibility in the corrosion curves obtained, as can be seen in Figure 308. Film growth rates for these two

TABLE 106. PARAMETERS FOR CORROSION OF ALLOY A-288 IN REFRESHED WATER AT $260^\circ C$

Parameters	Specimen Number				Average
	1	2	3	4	
f , Oxide Diss. Rate, mg of Al, cm^{-2} , $days^{-1}$	0.035	0.037	0.027	0.025	0.031
$2k_p$, Par. Growth Const., mg^2 , cm^{-4} , $days^{-1}$	0.132	0.155	0.159	0.162	0.152
g , mg, cm^{-2}	0.40	0.60	0.61	0.46	0.52

106-8997 Rev. 1

FIG. 308. Effect of Corrosion Product Dissolution Rate on Corrosion of Aluminum Alloy A-288 Water at 260°C.

106-8995 Rev. 1

FIG. 309. Corrosion in Stagnant Water at 260°C.

specimens were nearly equal, but dissolution rates were significantly different. Apparently this type of result is a consequence of uneven refreshment at different locations in the test autoclave.

If the corrosion exposure is in a stagnant autoclave

where very little oxide dissolution will take place the corrosion should be parabolic, with the parabolic rate constant of Table 106. Comparison of this prediction with data from stagnant tests (Figure 309) shows this to be true.

APPENDIX

PUBLICATIONS, REPORTS, AND PATENTS

PUBLICATIONS

- Aldred, A. T., *Magnetization of Iron-Beryllium Alloys*, J. Appl. Phys. **37**, 671-674 (February 1966).
- Aldred, A. T., *Magnetization of Iron-Gallium and Iron-Arsenic Alloys*, J. Appl. Phys. **37**, 1344-1346 (March 1966).
- Alfred, L. C. R., *Theory of the Resistivity Change in a Metal Due to Multiple Point Imperfections*, Phys. Rev. **152**, 693-698 (December 9, 1966).
- Alfred, L. C. R. and Fisher, E. S., *Temperature Variation of Dislocation Widths in HCP Metals*, Bull. IMD-AIME **1**(1), 53 (1966). ABSTRACT
- Arenberg, C. A. and Blewitt, T. H., *Radiation Hardness in Copper Single Crystals*, Bull. Am. Phys. Soc. **11**, 209 (March 1966). ABSTRACT
- Atlas, L. M., *Statistical Model for Oxygen Vacancies and Reduced Cations in a Fluorite Lattice*, Bull. Am. Cer. Soc. **45** No. 4, 379 (April 1966). ABSTRACT
- Atlas, L. M. and Schlehman, G. J., *Defect Equilibria of PuO_{2-x} , 1100°C to 1600°C*, Thermodynamics, Proc. IAEA Symposium, Vienna, July 22-27, 1965, International Atomic Energy, Vienna, Vol. II, pp. 407-421 (1966).
- Atlas, L. M., Schlehman, G. J., and Readey, D. W., *Defect in PuO_{2-x} : Density Measurements at High Temperature*, J. Am. Cer. Soc. **49** No. 11, 624-625 (November 1966).
- Ayer, J. E. and Soppet, F. E., *Vibratory Compaction. II. Compaction of Angular Shapes*, J. Am. Cer. Soc. **49**, 207-210 (April 1966).
- Bardos, D. I., *The Effect of Aluminum on the Saturation Moment of Fe-Ni Alloys*, University of Illinois (Work Performed at ANL) (September 1966). THESIS
- Bardos, D. I., Aldred, A. T., and Beck, P. A.,* *The Effect of Aluminum on the Saturation Moments of Fe-Ni Alloys*, IEEE 12th Annual Conference on Magnetism and Magnetic Materials, November 15-18, 1966, Washington, D. C. ABSTRACT M10
- Baskin, Y., *Melting Point Determination of Uranium Monophosphide*, Nucl. Sci. & Eng. **24**(4), 332-335 (April 1966).
- Baskin, Y., *Phase Studies in the Systems UP- UO_2* , Industrial Heating, p. 134 (January 1966).
- Baskin, Y., *Preparation and Properties of Uranium Metaphosphate $U(PO_3)_4$* , Bull. Am. Cer. Soc. **45**(4), 453 (1966). ABSTRACT
- Baskin, Y., *Properties of Uranium Monophosphide*, Bull. Am. Cer. Soc. **45**(4), 451 (1966). ABSTRACT
- Baskin, Y., *Properties of Uranium Monophosphide*, J. Am. Cer. Soc. **49**(10), 541-546 (October 1966).
- Baskin, Y. and Prasad, N. S. K., *Studies on TTA Complexes with Metal Ions—III. Investigation of Uranyl-TTA Complex in the Solid State*, J. Inorganic & Nucl. Chem. **28**(2), 461-466 (February 1966).
- Baskin, Y. and White, G. D., *Solid Solubility Among NaCl-Type Uranium Compounds*, Industrial Heating, p. 138 (January 1966).
- Beck, W. N. and Fousek, R. J., *Fission Gas Release and Microstructural Changes in High Burnup U-Pu Fast Breeder Alloys*, Trans. ANS **9**(2), 415 (1966). SUMMARY
- Berger, H., *Characteristics of a Thermal Neutron Television Imaging System*, Matls. Eval. **24**, 475-481 (September 1966).
- Berger, H., *Nuclear Techniques for Nondestructive Testing, RADIOISOTOPES FOR AEROSPACE, PART I. ADVANCES AND TECHNIQUES*, Plenum Press, New York, pp. 331-345 (1966).
- Berger, H. and Beck, W. N., *Neutron Television Inspection of Radioactive Fuel Capsules*, Trans. ANS **9**(2), 597 (1966). SUMMARY
- Berger, H. and Kraska, I. R., *Characteristics of an Infrared Vidicon Television System*, Matls. Eval. **24**(4), 197-200 (April 1966).
- Berger, H., Kraska, I. R., Niklas, W. F.,† and Schmidt, A.,† *A Thermal Neutron Image Intensification System*, IEEE Trans. on Nuclear Science **13**(2), 79-83 (April 1966).
- Berndt, A. F., *A Gamma Phase in the Plutonium-Mercury System*, J. Less-Common Metals **11**, 216-219 (1966).
- Berndt, A. F., *Growth of Large Grains in a Gallium-stabilized Delta-plutonium Alloy*, J. Less-Common Metals **10**, 71-72 (1966). SHORT COMMUNICATION
- Blewitt, T. H., *Radiation Damage*, Proc. Symp. on Pulsed High Intensity Fission Neutron Sources, USAEC, Washington, February 1965, CONF-650217, pp. 108-110.
- Brodsky, M. B. and Griffin, N. J., *Hall Effect and Electrical Resistivity of Neptunium and Americium*, Bull. Am. Phys. Soc. II **11**, 92 (January 1966). ABSTRACT
- Burt, W. R. and Mayfield, R. M., *Techniques for Extrusion of Small Diameter Refractory Metal Tube Blanks*, REFRAC-TORY METALS & ALLOYS III—APPLIED ASPECTS (AIME Symp. on Applications of Refractory Metals, December 9-10, 1963, Los Angeles, California) Gordon & Breach Sci. Pub., New York, 75-84 (1966).
- Carrea, A. J. and Handwerk, J. H., *Reaction Sintering of Uranium Sesquioxide (U_3Si_2)*, Industrial Heating, p. 138 (January 1966).
- Cotterill, R. M. J., *A Brief Review of Energy Calculations for Clusters of Point Defects in Metals*, AERE-R-5269, I, Report of Consultants' Symposium, AERE, Harwell, England, July 4-7, 1966, 144-172 (1966).
- Cotterill, R. M. J., *A Comparison Between Neutron Damage in Annealed Gold and in Quenched Gold*, Appl. Phys. Letters **9**(1), 29-31 (July 1966).
- Cotterill, R. M. J. and Doyama, M., *Atomic Configuration and Energy of Edge Dislocations in bcc Metals*, Bull. Am. Phys. Soc. **11**(2), 219 (March 1966). ABSTRACT
- Cotterill, R. M. J. and Doyama, M., *Atomistic Approach to the Peierls-Nabarro Barrier for Edge Dislocations*, Bull. Am. Phys. Soc. **11**(3), 346 (April 1966). ABSTRACT
- Cotterill, R. M. J. and Doyama, M., *Binding Energies of*

* University of Illinois, Champaign, Illinois.

† The Rauland Corporation, Chicago, Illinois.

- Vacancy Clusters in Copper, Bull. Am. Phys. Soc. **11**(4), 460 (June 1966). ABSTRACT
- Cotterill, R. M. J. and Doyama, M., *The Energy and Atomic Configuration of Complete and Dissociated Dislocations. I. Edge Dislocation in an fcc Metal*, Phys. Rev. **145**, 465-478 (May 13, 1966).
- Cotterill, R. M. J. and Doyama, M., *Investigation of the Stability of Voids in fcc Metals*, Bull. Am. Phys. Soc. II **11**(1), 48 (January 1966). ABSTRACT
- Cotterill, R. M. J. and Doyama, M., *Oscillatory Potential Calculations of the Vacancy Formation Energy in Aluminum*, Bull. Am. Phys. Soc. **11**(3), 416 (April 1966). ABSTRACT
- Cotterill, R. M. J. and Doyama, M., *A Study of Small Vacancy Clusters on {111} Planes in Copper*, AERE-R-5269, I, Report of Consultants' Symposium, AERE, Harwell, England, July 4-7, 1966, 211-217 (1966).
- Darby, J. B., Jr., *The Design and Performance of a Twin-Well Liquid Metal Solution Calorimeter*, 21st Annual Calorimetry Conference, University of Colorado, Boulder, Colorado, June 22-24, 1966, Paper IIIC. ABSTRACT
- Darby, J. B., Jr., *The Relative Heats of Formation of Solid Gold-Palladium Alloys*, Acta Met. **14**, 265-270 (March 1966).
- Darby, J. B., Jr., Kleb, R., and Kleppa, O. J.,* *Twin Liquid Metal Solution Calorimeter*, Rev. Sci. Instr. **37**(2), 164-167 (February 1966).
- Darby, J. B., Jr., Myles, K. M., and Pratt, J. N.,† *Thermodynamic Properties of Pd-Cd and of Pd-Sb Alloys*, IMD-AIME **1**(2), 14 (1966). ABSTRACT
- Darby, J. B., Jr., Myles, K. M., and Pratt, J. N.,† *Thermodynamic Properties of Pd-Cd and of Pd-Sb Alloys*, J. Metals **18**, 1162 (1966). ABSTRACT
- de Wette, F. W.,‡ Cotterill, R. M. J., and Doyama, M., *Lattice Dynamics of Copper with a Morse Potential*, Phys. Letters **23**(5), 309-311 (October 31, 1966).
- de Wette, F. W.,‡ Cotterill, R. M. J., and Doyama, M., *Lattice Dynamics of fcc Crystals with a Morse Potential*, Bull. Am. Phys. Soc. **11**(2), 249 (March 1966). ABSTRACT
- diNovi, R. A., *Relationship Between the Effective Thermal Conductivity and Ultrasonic Transmission for Copper Braze Bonds*, Appl. Mats. Res., 162-167 (July 1966).
- Doyama, M. and Cotterill, R. M. J., *Application of Oscillatory Potentials to Atomistic Calculations of Lattice Defects*, Bull. Am. Phys. Soc. II **11**(1), 48 (January 1966). ABSTRACT
- Doyama, M. and Cotterill, R. M. J., *Atomic Configuration and Energy of Screw Dislocations in bcc Metals*, Bull. Am. Phys. Soc. **11**(4), 460 (June 1966). ABSTRACT
- Doyama, M. and Cotterill, R. M. J., *Energy and Atomic Configurations of Complete and Dissociated Dislocations. II. Screw Dislocation in an fcc Metal*, Phys. Rev. **150**, 448-455 (October 14, 1966).
- Doyama, M. and Cotterill, R. M. J., *Frenkel Pairs in fcc Metals*, Bull. Am. Phys. Soc. **11**(3), 346 (April 1966). ABSTRACT
- Doyama, M. and Cotterill, R. M. J., *Investigation of Metallic Surfaces in the Central-Force Approximation*, Bull. Am. Phys. Soc. **11**(2), 250 (March 1966). ABSTRACT
- Doyama, M. and Cotterill, R. M. J., *Peierls-Nabarro Barrier Calculations for Screw Dislocations*, Bull. Am. Phys. Soc. **11**(3), 416 (April 1966). ABSTRACT
- Doyama, M. and Cotterill, R. M. J., *Vacancy-Impurity Binding Energy in Aluminum*, Phys. Letters **23**(1), 58-59 (October 3, 1966).
- Dwight, A. E., *The Uranium-Rhodium Equilibrium Diagram Below 1100°C*, Abstract Bull. IMD-AIME **1**(1), 41 (1966). ABSTRACT
- Dwight, A. E., *ZrX₂ Compounds*, IMD-AIME **1**(2), 52 (1966). ABSTRACT
- Dwight, A. E., Downey, J. W., and Conner, R. A., Jr., *Laves Phases of the Scandium Group Elements with Ruthenium, Rhodium, Osmium, Iridium, and Platinum*, Trans. Met. Soc. AIME **236**, 1509 (1966).
- Fisher, E. S., *Temperature Dependence of the Elastic Moduli in Alpha-Uranium Single Crystals, Part IV (298° to 923°K)*, J. Nucl. Matls. **18**(1), 39-54 (January 1966).
- Fisher, E. S. and Dever, D., *Temperature Dependence of the Elastic Moduli in Single Crystal Rhenium and Ruthenium*, Abstract Bull. IMD-AIME **1**(1), 13 (1966). ABSTRACT
- Flinn, J. E. and Gilbert, E. R., *Discussion: High Temperature Creep of Tantalum*, Trans. AIME **236**, 1512 (October 1966).
- Flinn, J. E. and Mayfield, R. M., *Evaluation of New Fabrication Techniques for High-Quality Refractory Metal Tubing*, REFRACTORY METALS & ALLOYS III—APPLIED ASPECTS (AIME Symp. on Applications of Refractory Metals, December 9-10, 1963, Los Angeles, California) Gordon & Breach Sci. Pub., New York, 125-135 (1966).
- Forlano, R. J., Allen, A. W., and Beals, R. J., *Elasticity and Anelasticity of Uranium Oxides at Room Temperature*, Bull. Am. Cer. Soc. **45**(4), 451 (1966).
- Friddle, R. J., Liptai, R. G., Lloyd, L. T., and Odie, M. D., *Metallographic and X-Ray Studies of Alpha Plutonium*, ADVANCES IN METALLOGRAPHY (Technical Papers of the 20th Metallographic Conference, May 18-20, 1966, Denver, Colorado) RFP-658, pp. 185-194 (1966).
- Friddle, R. J., Liptai, R. G., and Lloyd, L. T., *On the Use of Alkali Metals for Pressure Transmission in High-Pressure Investigation*, Abstract Bull. IMD-AIME **1**(1), 35 (1966). ABSTRACT
- Friddle, R. J., Liptai, R. G., and Lloyd, L. T., *The Use of Alkali Metals for Transmission of Hydrostatic Pressure*, Trans. AIME **236**, 1090-1091 (July 1966). LETTER
- Geballe, T. H.,§ Matthias, B. T.,§ Andres, K.,§ Fisher, E. S., Smith, T. F.,¶ Zachariasen, W. H.,|| *Superconductivity of Alpha-Uranium and the Role of 5f Electrons*, Science **152**(3723), 755-757 (May 6, 1966).
- Gilbert, E. R., *Discussion: Effects of Grain Size on Tensile and Creep Properties of Arc-Melted and Electron-Beam-Melted Tungsten at 2250° to 4140°F*, Trans. AIME **236**, 1511-1512 (October 1966).
- Goldak, J.,** Lloyd, L. T., and Barrett, C. S.,†† *Lattice Parameters, Thermal Expansion, and Grüneisen Coefficients of Zirconium, 4.2° to 1130°K*, Phys. Rev. **144**(2), 478-484 (April 15, 1966).
- Gruber, E. E., *Calculated Size Distributions of Bubbles in Solids for Surface Diffusion Migration and Coalescence*, Abstract Bull. IMD-AIME **1**(1), 7 (1966). ABSTRACT
- Gruber, E. E. and Mullins, W. W.,‡‡ *Extended Analysis of Surface Scratch Smoothing*, Acta Met. **14**, 397-403 (March 1966).

§ Bell Telephone Labs., Whippany, New Jersey.

¶ University of California, Berkeley, California.

|| University of Chicago, Chicago, Illinois.

** Carleton University, Ottawa, Canada.

†† University of Chicago, Chicago, Illinois.

‡‡ Carnegie-Mellon Institute, Pittsburgh, Pennsylvania.

* Consultant, University of Chicago, Chicago, Illinois

† ANL and University of Birmingham, England.

‡ University of Texas, Austin, Texas.

- Hart, R. K., *Composite Aluminum-Nickel Evaporated Films*, J. Appl. Phys. **37**, 2918-2919 (June 1966). LETTER
- Hart, R. K., *Electron Diffraction Techniques and Their Applications to the Study of Surface Structure*, PROG. NUCL. ENERGY, SERIES IX. ANALYTICAL CHEMISTRY, Vol. 7, pp. 3-20, Pergamon Press (1966).
- Hart, R. K., Kassner, T. F., and Maurin, J. K., *Residual Gas Analysis in an Auxiliary Pumped Siemens Electron Microscope*, PROCEEDINGS OF 6th INTERNATIONAL CONGRESS FOR ELECTRON MICROSCOPY, KYOTO, August 28-September 4, 1966, Vol. 1, 161-162, Maruzen Co., Ltd., Tokyo, Japan (1966).
- Hart, R. K. and Maurin, J. K., *Growth of Oxide Nuclei on Iron*, PROCEEDINGS OF SIXTH INTERNATIONAL CONGRESS FOR ELECTRON MICROSCOPY, KYOTO, August 28-September 4, 1966, Vol. I, 539-540, Maruzen Co., Ltd., Tokyo, Japan (1966).
- Hart, R. K. and Pilney, D. G., *A Compact Vacuum-Path 20 Scanner*, THE ELECTRON MICROSCOPE, Proc. Symp., Washington, October 12-15, 1964, 472-479, John Wiley & Sons, Inc. (1966).
- Hehemann, R. F. and Ziegler, S. T., *Superconductivity in Aged Zirconium-Niobium Alloys*, Trans. AIME **236**, 1594-1596 (November 1966).
- Henninger, E. H.,§ Buschert, R. C.,§ and Heaton, L., *Atomic Structure and Correlation in Liquid Binaries by X-Ray and Neutron Diffraction with Application to NaK*, J. Chem. Phys. **44**, 1758-1764 (March 1966).
- Horak, J. A. and Blewitt, T. H., *Effect of Irradiation of Precipitation in Al-Zn Alloys*, Bull. Am. Phys. Soc. **11**, 210 (March 1966). ABSTRACT
- Kastner, J., Berger, H., and Kraska, I. R., *LiF Thermoluminescence for Neutron Image Storage*, Nucl. Appl. **2**, 252-253 (June 1966).
- Kern, R. S.* and Beals, R. J., *Thermal Properties of Compositions in the System UO_2 - ZrO_2 - CaO* , Bull. Am. Cer. Soc. **45**, 821 (September 1966). ABSTRACT
- Kiewit, D. A.,† Rechten, J. J., Brittain, J. O.,† *The Reflectance of the Intermetallic Compounds NiAl and CoAl*, J. Phys. Soc. Japan **21**(11), 2380-2392 (November 1966).
- Kimball, C. W., Kalvius, G. M., and Nevitt, M. V., *Mössbauer Resonance of Au^{197} Nuclei in Ordered Binary Alloys of Gold with Rare Earth*, Bull. Am. Phys. Soc. **11**, 267 (March 1966). ABSTRACT
- Kimball, C. W., Phillips, W. C., Nevitt, M. V., and Preston, R. S., *Magnetic Hyperfine Interactions and Electric Quadrupolar Coupling in Alloys of Iron with the Alpha-Manganese Structure*, Phys. Rev. **146**(2), 375-378 (June 10, 1966).
- Kimball, C. W., Tison, J. K.,‡ and Nevitt, M. V., *Hyperfine Interactions at Fe^{57} Nuclei in Intermetallic Compounds of Fe + Mn with the β -Manganese Structure*, IEEE 12th Annual Conference on Magnetism and Magnetic Materials, November 15-18, 1966, Washington, D. C., Abstract I11 (1966). ABSTRACT
- Kittel, J. H., *Outlook Brightens for Metallic Plutonium Fuels*, Nucleonics **24**(7), 70-71 (July 1966).
- Kittel, J. H. and Beck, W. N., *Behavior of Refractory Metal-Clad Plutonium Alloy Fuel Under Irradiation*, REFRAC-TORY METALS & ALLOYS III—APPLIED ASPECTS (AIME Symp. on Applications of Refractory Metals, December 9-10, 1963, Los Angeles, California) Gordon & Breach Sci. Pub., New York, 597-607 (1966).
- Kocks, U. F., *On the Spacing of Dispersed Obstacles*, Acta Met. **14**, 1629-1631 (November 1966).
- Kocks, U. F., *Work-Hardening in Stage III*, IMD-AIME **1**(2), 31 (1966). ABSTRACT
- Koppenaar, T. J., *Comments on "The Effect of Fast Neutron Damage on the Deformation of Copper-Tin Alloys,"* Acta Met. **14**, 681-682 (May 1966). LETTER
- Koppenaar, T. J. and Arsenault, R. J.,¶ *Some Notes on the Strengthening Mechanism in Neutron Irradiated Copper Single Crystals*, Physica Status Solidi **17**, 27-33 (1966).
- Koppenaar, T. J., Yeh, W. C. T.,|| and Cotterill, R. M. J., *Lattice Defects in Neutron Irradiated α Cu Solid Solution Alloys*, Phil. Mag. **13**(124), 867-871 (April 1966). LETTER
- Kruger, O. L., *Phase Relations and Structures in Uranium-Plutonium-Fissium Alloys*, J. Nucl. Matls. **19**(1), 29-41 (April 1966).
- Kruger, O. L. and Moser, J. B., *Electrical Resistivities and Seebeck Coefficients of Some Plutonium Compounds*, Bull. Am. Cer. Soc. **45**(4), 449 (April 1966). ABSTRACT
- Kruger, O. L. and Moser, J. B., *Preparation of the Sulphides and Phosphides of Plutonium*, J. Inorg. Nucl. Chem. **28**, 825-832 (March 1966).
- Lam, D. J. and Myles, K. M., *The Magnetic Susceptibilities of Pd-Cd, Pd-Sb, and Pt-Cu Binary Alloys*, IMD-AIME **1**(2), 55 (1966). ABSTRACT
- Lam, D. J. and Myles, K. M., *The Magnetic Susceptibilities of Pd-Cd, Pd-Sb, and Pt-Cu Binary Alloys*, J. Phys. Soc. of Japan **21**(8), 1503-1507 (August 1966).
- LaVelle, E. B.** and Stone, C. C., *Process Application Analysis for MIG Welding*, British Welding Journal **13**(7), 407-413 (July 1966).
- Levin, H. A., Ruther, W. E., and Greenberg, S., *Corrosion of Refractory Metal Alloys in Oxygen-Contaminated Sodium*, Proc. AEC-NASA Liquid Metals Information Meeting, Gatlinburg, Tennessee, April 21-23, 1965, USAEC Publication CONF-650411, p. 63 (1966). ABSTRACT
- Levitani, J., Draley, J. E., and VanDrunen, C. J., *Studies in Zirconium Oxidation*, ANL-7252 (December 1966).
- Link, L. E., Ayer, J. E., Hub, K. A., Mecham, W. J., Trice, V. G., Jr., and Weills, J. T., *A Large Metal-Fueled Fast Reactor Study—Part II. Core Design and Fuel Cycle*, PROCEEDINGS OF THE CONFERENCE ON SAFETY, FUELS, AND CORE DESIGN IN LARGE FAST POWER REACTORS, October 11-14, 1965, ANL-7120, pp. 94-103 (1966).
- Liptai, R. G. and Friddle, R. J., *The Effects of High Pressure on the Alpha $\rightleftharpoons$ Beta Transformation in Plutonium*, J. Nucl. Matls. **20**(1), 48-56 (July 1966).
- Liptai, R. G. and Friddle, R. J., *The Phase Diagram of Plutonium at Pressures up to 75 kbar*, J. Less-Common Metals **10**, 292-294 (April 1966). LETTER
- Liptai, R. G., Lloyd, L. T., and Friddle, R. J., *Effects of High Pressure and Temperature on the Microstructure of Plutonium*, Abstract Bull. IMD-AIME **1**(1), 35 (1966). ABSTRACT
- Lloyd, L. T. and Barrett, C. S., *Thermal Expansion of Alpha-Uranium*, J. Nucl. Matls. **18**(1), 55-59 (1966). LETTER
- Lloyd, L. T., Liptai, R. G., and Friddle, R. J., *The Effects of*

§ Purdue University, West Lafayette, Indiana.

* Phillips Petroleum Company.

† Northwestern University, Evanston, Illinois.

‡ ANL and Northern Illinois University, DeKalb, Illinois.

¶ Oak Ridge National Lab., Oak Ridge, Tennessee.

|| Michigan Technological University, Houghton, Michigan.

** HAPCO, Richland, Washington.

- High Pressure and Temperature on the Microstructure of Alpha-Uranium, *J. Nucl. Matls.* **19**(2), 173-180 (May 1966).
- Lloyd, L. T., Liptai, R. G., and Friddle, R. J., *Effects of Phase Transformations at High Pressures and Temperatures on the Microstructure of Alpha-Uranium*, Abstract Bull. IMD-AIME **1**(1), 35 (1966) ABSTRACT
- Loewenstein, W. B. and Blumenthal, B., *Mixed Fuel-Cycle Fast Breeder Reactors. Nuclear, Safety, and Materials Considerations*, PROCEEDINGS OF THE CONFERENCE ON SAFETY, FUELS, AND CORE DESIGN IN LARGE FAST POWER REACTORS, October 11-14, 1965, ANL-7120, pp. 751-758 (1966).
- Macherey, R. E., Kelman, L. R., and Kittel, J. H., *Metal Fuels for Fast Reactors*, PROCEEDINGS OF THE CONFERENCE ON SAFETY, FUELS, AND CORE DESIGN IN LARGE FAST POWER REACTORS, October 11-14, 1965, ANL-7120, pp. 289-300 (1966).
- Matras, S., *Metallographic Holding Fixture Permits Polishing of Soft Metals on Vibratory Lapping Machine*, AEC-NASA Tech. Brief 66-10562 (December 1966).
- Merkle, K. L., *Radiation-Induced Point Defect Clusters in Copper and Gold*, AERE-R-5269, I, Report of Consultants' Symposium, AERE, Harwell, England, July 4-7, 1966, 8-37 (1966).
- Merkle, K. L., *Radiation-Induced Point Defect Clusters in Copper and Gold, Part I*, Phys. Stat. Sol. **18**, 173 (1966).
- Merkle, K. L. and Singer, L. R., *Radiation Annealing in Gold near 4.2°K*, Bull. Am. Phys. Soc. **11**, 209 (March 1966). ABSTRACT
- Messier, D. R. and Hurum, W. H., *Tungsten Deposition From a Tungsten Mesh Heating Element in Vacuum Above 2450°K*, Rev. Sci. Instr. **37**(11), 1610-1611 (1966). NOTE
- Moser, J. B. and Kruger, O. L., *Preparation of Plutonium Phosphide by Direct Combination of the Elements*, J. Less-Common Metals **10**(6), 402-407 (1966).
- Moser, J. B. and Kruger, O. L., *Thermal Conductivity and Heat Capacity of Uranium Compounds*, Bull. Am. Cer. Soc. **45**, 449 (April 1966). ABSTRACT
- Murphy, W. F. and Stroh, H. E., *Burst Tests on Stainless-Steel Tubular Fuel Jackets Irradiated to 10^{22} n/cm² in a Fast-Flux Reactor (EBR-II)*, Trans. ANS **9**(1), 51 (June 1966).
- Neimark, L. A., *The Irradiation Behavior of Vibratorily Compacted UC-20w/oPuC Powders*, Trans. ANS **9**(2), 415 (1966). SUMMARY
- Neimark, L. A., Ayer, J. E., Kruger, O. L., Latimer, T. W., and Walters, C. M., *Mixed-Carbide Fuels for Fast Reactors*, PROCEEDINGS OF THE CONFERENCE ON SAFETY, FUELS, AND CORE DESIGN IN LARGE FAST POWER REACTORS, October 11-14, 1965, ANL-7120, pp. 314-327 (1966).
- Niklas, W. F.* and Berger, H., *A Thermal Neutron Image Intensifier*, ADVANCES IN ELECTRONICS AND ELECTRON PHYSICS, VOL. 22B. PHOTOELECTRONIC IMAGE DEVICES, p. 781, Ed. by J. D. McGee, D. McMullan, and E. Kahan, Academic Press (1966). ABSTRACT
- O'Boyle, D. R., Rhude, H. V., and Blumenthal, B., *Progress in the Development of Fast-Reactor Metal Fuels*, Trans. ANS **9**(1), 1 (June 1966). SUMMARY
- Penn, D. R., *Magnetic Phases for a Simple Model of the Transition Metals*, Bull. Am. Phys. Soc. **11**, 238 (March 1966). ABSTRACT
- Preston, R. S., Lam, D. J., Nevitt, M. V., Van Ostenburg, D. O., and Kimball, C. W., *Crystal Structures of V-Fe Alloys as Determined by the Mossbauer Effect in Fe⁵⁷*, Phys. Rev. **149**, 440-449 (September 16, 1966).
- Readey, D. W., *Chemical Potentials and Initial Sintering in Pure Metals and Ionic Compounds*, J. Appl. Phys. **37**(6), 2309-2312 (May 1966).
- Readey, D. W., *Mass Transport and Sintering in Impure Ionic Solids*, J. Am. Cer. Soc. **49**(7), 366-369 (July 1966).
- Readey, D. W., *Theory of Mass Transport and Sintering in Impure Ionic Compounds*, Bull. Am. Cer. Soc. **45**, 365 (April 1966). ABSTRACT
- Readey, D. W. and Handwerk, J. H., *Nuclear Fuel Materials*, Bull. Am. Cer. Soc. **45**(4), 355 (April 1966). ABSTRACT
- Readey, D. W. and Kuczynski, G. C., *Sublimation of Aluminum Oxide in Hydrogen*, J. Am. Cer. Soc. **49**, 26-29 (January 1966).
- Reinke, C. F., Robinson, L. E., and Ivins, R. O., *High Temperature Thermometry—Service and Related Experience*, Proc. High Temperature Thermometry Seminar, Washington, February 24-26, 1965, WASH-1067, pp. 22.1-22.2 (March 1966).
- Renken, C. J. and Selner, R. H., *Refractory Metal Tubing Inspection Using Ultrasonic and Pulsed Eddy Current Methods*, Matls. Eval. **24**(5), 257-262 (May 1966).
- Ross, J. W. and Lam, D. J., *The Magnetic Susceptibility of Neptunium Oxide and Carbide Between 4.2°K and 350°K*, IEEE 12th Annual Conference on Magnetism and Magnetic Materials, November 15-18, 1966, Washington, D. C., Abstract U6 (1966). ABSTRACT
- Rossin, A. D., *Hydrogen in Irradiated Pressure Vessel Steel*, Trans. ANS **9**(2), 389 (1966). SUMMARY
- Rothman, S. J., Bastar, R., Hines, J. J., and Rokop, D., *The Anisotropy of Self-Diffusion in Alpha-Uranium*, Trans. AIME **236**, 897-899 (June 1966).
- Rothman, S. J., Peterson, N. L., Hines, J. J., and Bastar, R., *Isotope Effect for the Diffusion of Zinc in Silver*, Abstract Bull. IMD-AIME **1**(1), 8 (1966). ABSTRACT
- Ruther, W. E., Schlueter, R. R., Lee, R. H., and Hart, R. K., *Corrosion Behavior of Steels and Nickel Alloys in Superheated Steam*, Corrosion **22**, 147-155 (May 1966).
- Savage, H., *Isothermal Drop Calorimeter for Alpha-Active, Pyrophoric Materials*, Rev. Sci. Instr. **37**, 1062-1064 (August 1966).
- Shuck, A. B. and Handwerk, J. H., *Plutonium Management at Argonne*, Proc. Commercial Plutonium Fuels Conf., Washington, D. C., March 1-2, 1966, USAEC Report CONF-660308, pp. 159-164 (1966).
- Shuck, A. B., Lotts, A. L.,† and Drumheller, K.,‡ "The Remote Fabrication of Reactor Fuels," REACTOR TECHNOLOGY—Selected Reviews—1965, pp. 71-148, Ed. L. E. Link, USAEC TID-8541.
- Sidhu, S. S., Vogelsang, W., and Anderson, K. D., *Antiferromagnetic Ordering of Uranium Monophosphide*, Structure de la Matière, Vol. XXVII (4), p. 610, Abstract 27-6-10668 (1966).
- Sidhu, S. S., Vogelsang, W., and Anderson, K. D., *The Antiferromagnetism of Uranium Monophosphide*, J. Phys. Chem. Solids, **27**, 1197-1200 (1966).
- Spokas, J. J.,§ Sowers, C. H., and Van Ostenburg, D. O., *NMR in Aluminum-Transition Metal Compounds*, Bull. Am. Phys. Soc. **11**, 482 (June 1966). ABSTRACT

† Oak Ridge National Lab., Oak Ridge, Tennessee.

‡ Pacific Northwest Lab., Richland, Washington.

§ St. Procopius College, Lisle, Illinois.

* Rauland Corporation, Chicago, Illinois.

- Taylor, J. C.,* Mueller, M. H., and Hitterman, R. L., *Crystal Structure of Thorium Nitrate Pentahydrate by Neutron Diffraction*, Acta Cryst. **20**, 842-851 (June 1966).
- Van Ostenburg, D. O. and Alfred, L. C. R., *Knight Shifts in Dilute Silver Alloys*, Bull. Am. Phys. Soc. **11**, 916 (December 1966). ABSTRACT
- Van Ostenburg, D. O., Sowers, C. H., and Spokas, J. J.,† *Nuclear-Spin-Lattice Relaxation of V^{51} in V-Fe Alloys*, Phys. Letters **20**(5), 461-462 (March 15, 1966).
- Van Ostenburg, D. O., Spokas, J. J.,‡ and Sowers, C. H., *Knight Shift and Nuclear-Spin-Lattice Relaxation in FeAl, RuAl and OsAl Intermetallic Compounds*, Bull. Am. Phys. Soc. **11**, 219 (March 1966). ABSTRACT
- Wang, J. Y. N., *Lithium Corrosion Studies at Elevated Temperatures*, Proc. AEC-NASA Liquid Metals Information Meeting, Gatlinburg, Tennessee, April 21-23, 1965, USAEC Publication CONF-650411, p. 137 (1966). ABSTRACT
- Walter, C. M. and Lahti, J. A., *Compatibility of U-Pu-Fz Fuel Alloys with Potential Cladding Materials*, Nucl. Appl. **2**, 308-319 (August 1966).
- * AAEC Research Establishment, Sutherland, N.S.W., Australia.
- Westlake, D. G., *On Stress Orientation of Zirconium Hydride in a Single Crystal of Zirconium*, Trans. AIME **236**, 1229 (August 1966). NOTE
- Westlake, D. G., *On {10.1} Twinning in the hcp Structure*, Acta Met. **14**, 442-443 (March 1966). LETTER
- Westlake, D. G. and Gray, W. R., *A Pitfall in the Preparation of Metal-Hydrogen Alloys for Transmission Electron Microscopy*, Appl. Phys. Letters **9**(1), 3-4 (July 1966)
- White, G. D., *Oxidation Studies in Air and Water-Saturated Argon of Compositions in the System UC-US*, Industrial Heating, p. 134 (January 1966).
- White, G. D. and Baskin, Y., *Phase Studies in the System UC-UP*, Industrial Heating, p. 138 (January 1966).
- Youngdahl, C. A., *Corrosion Test Coupons—Mechanical Cleaning*, Mals. Protect. **5**(10), 53-54 (October 1966).
- Youngdahl, C. A. and Greenberg, S., *Polarization Studies in Oxygen-Contaminated Sodium*, Proc. AEC-NASA Liquid Metals Information Meeting, Gatlinburg, Tennessee, April 21-23, 1965, USAEC Publication CONF-650411, p. 74 (1966). ABSTRACT
- Zegler, S. T., *Compatibility Studies of Uranium-Plutonium-Zirconium Fuels with Iron-Base Cladding Alloys*, Trans. Ans **9**(1), 2 (June 1966). SUMMARY

REPORTS

- ANL-6236 Mori, S., Draley, J. E., and Loess, R. E., *Crevice-Galvanic Corrosion of Aluminum* (June 1966).
- ANL-6283 Kramer, W. C., McCuaig, F. D., Beatty, R. A., Bean, C. H., and Noland, R. A., *Fabrication of Spiked-Core Fuel Elements for the Experimental Boiling Water Reactor* (November 1965).
- ANL-6417 Burt, W. R., Jr., McGowan, R. D., and Bean, C. H., *The Fabrication and Testing of Depleted Uranium Blanket Slugs for EBR-II* (November 1965).
- ANL-6568 Peterson, N. L. and Rothman, S. J., *Diffusion in Gamma Uranium* (November 1965).
- ANL-6621 Beatty, R. A., McCuaig, F. D., and Bean, C. H., *Procurement and Processing of EBR-I Core IV Uranium and Hardware* (March 1966).
- ANL-6832 Carlander, R., *Examination of EBWR Core 1A Fuel* (June 1966).
- ANL-6893 Lynch, E. D. and Handwerk, J. H., *Fabrication and Evaluation of Thoria-Urania Fuel Material* (November 1965).
- ANL-6894 Lynch, E. D., *Studies of Stoichiometric and Hyperstoichiometric-Solid Solutions in the Thoria-Urania System* (December 1965).
- ANL-6943 Taylor, J. C. and Mueller, M. H., *A Neutron-Diffraction Study of Uranyl Nitrate Hexahydrate* (November 1965).
- ANL-6950 Ayer, J. E., Jones, D. A.,* Ebert, D. D.,† Buckzwinski, T. A.,‡ and Sana, J. V.,§ *A Cost Estimate for Remote Refabrication of Metallic Fuels* (March 1966).
- ANL-6969 Tope, W. G., *Production of Plutonium Monocarbide by Reaction of Elemental Plutonium and Carbon* (July 1965).
- ANL-6975 Matras, S., *Vibratory Grinding and Polishing of Metallographic Specimens* (November 1965).
- ANL-6981 Brooks, E. J.* and Kramer, W. C., *Tungsten-Rhenium Alloy Thermocouples and Their Use in a UO_2 -Fueled Reactor* (November 1965).
- ANL-6985 Kassner, T. F., *A Convective Diffusion Study of the Dissolution Kinetics of 304 Stainless Steel in the Bismuth-Tin Eutectic Alloy* (November 1965).
- ANL-7001 Link, L. E., Ayer, J. E., Butler, D. K., Hub, K. A., Lowenstein, W. B., Mecham, W. J., Meneghetti, D., Thompson, D. H., Trice, V. G., Jr., and Weills, J. T., *1000-MW(e) Metal-Fueled Fast Breeder Reactor* (June 1966).
- ANL-7042 Berger, Harold, *A Television System for Ultrasonic Imaging* (January 1966).
- ANL-7049 Long, J. K.,* Kelman, L. R., McVean, R. L.,* Novick, M.,* Shuck, A. B., and Thalgott, F. W.,* *Safety Analysis of the Operation of ZPR-8 with Fuel Loadings up to 430 kg of Plutonium* (December 1965).
- ANL-7062 Lynch, E. D., *Glassy Materials for Nuclear Reactor Applications* (November 1965).
- ANL-7070 Tottle, C. R.,† *Mechanical Properties of Uranium Compounds* (November 1965).
- ANL-7074 diNovi, R. A., *Correlation of the Heat Transfer Properties and Ultrasonic Transmission Properties of Bonds* (February 1966).
- ANL-7075 Ayer, J. E., Soppet, F. E., Talaber, G. J., Bieler, B. H.,‡ *Nuclear-Fuel-Element Loading by Vibratory Compaction—Uranium-Plutonium Carbide Specimens for EBR-II Irradiation* (February 1966).
- ANL-7078 Hart, R. K., *Corrections for X-Ray Intensity Data Obtained from Electron Microprobes* (November 1965).

* ANL-ISE.

† Georgia Tech.

‡ Marquette University.

§ Notre Dame.

- ANL-7079 Gruber, E. E., *On the Theory of Migration and Coalescence of Bubbles in Solids* (November 1965).
- ANL-7094 Walter, C. M., *Review of Status of Self-Diffusion in US, Un, UO₂, and UC* (November 1965).
- ANL-7101 Forlando, R. J., Allen, A. W.,* and Beals, R. J., *Elasticity and Anelasticity of Uranium Oxides at Room Temperature* (December 1965).
- ANL-7102 Hart, R. K. and Pilney, D. G., *Growth and Annealing of Evaporated Aluminum-Silicon Films* (November 1965).
- ANL-7119 Peterson, R. G., *A Facility for Studying Elastic Moduli as a Function of Temperature by an Ultrasonic Method; Measurements on Vanadium-20 w/o Titanium* (February 1966).
- ANL-7127 Burt, W. R., Jr., Kramer, W. C., Karasek, F. J., and Mayfield, R. M., *Improvements in Consolidation and Fabrication of Vanadium-20 w/o Titanium (TV-20)* (May 1966).
- ANL-7135 Rosen, M., Peterson, R. G., and Lloyd, L. T., *The Beta $\rightarrow$ Alpha Transformation in High-Purity Plutonium* (February 1966).
- ANL-7155 *Annual Progress Report for 1965, Metallurgy Division*
- ANL-7164 Dusek, J. T., *The Development and Fabrication of a Boron Absorption Tube for Spectrographic Analysis* (March 1966).
- ANL-7182 Sidhu, S. S., Heaton, L., Mueller, M. H., Campos, F. P., Anderson, K. D., and Zaubers, D. D., *The Use of Nuclear Null-Matrix in Neutron Diffraction Studies* (March 1966).
- ANL-7232 Gibbon, C. F., *Grain-Boundary Migration in Potassium Chloride Bicrystals* (August 1966).

PATENTS

- Ayer, James E. and Soppet, Frederick E., *Method and Apparatus for Vibratory Compaction*, Patent No. 3,261,378 (July 19, 1966).
- Baskin, Yehuda and Shalek, Peter D., *Uranium Monosulfide-Uranium Monophosphide Solid Solutions*, Patent No. 3,264,223 (August 2, 1966).
- Bean, Charles H., *Process of Making a Sintered Homogeneous Dispersion of Nuclear Fuel and Burnable Poison*, Patent No. 3,263,004 (July 26, 1966).
- Kruger, Owen L., Moser, John B., and Wrona, Bernard J., *Preparation of Plutonium Monosulfide and Plutonium Monophosphide*, Patent No. 3,282,656 (November 1, 1966).
- Renken, Claus J., *Pulsed Electromagnetic Field System for Nondestructive Testing*, Patent No. 3,229,197 (January 11, 1966).