DR 316

5-73
LA-5320-MS

INFORMAL REPORT

Hydrogen Absorption by AB_5 Compounds

los alamos
scientific laboratory

of the University of California

LOS ALAMOS, NEW MEXICO 87544

UNITED STATES
ATOMIC ENERGY COMMISSION
CONTRACT W-7405-ENG. 36

MASTER

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

This report was prepared as an account of work sponsored by the United States Government. Neither the United States nor the United States Atomic Energy Commission, nor any of their employees, nor any of their contractors, subcontractors, or their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness or usefulness of any information, apparatus, product or process disclosed, or represents that its use would not infringe privately owned rights.

In the interest of prompt distribution, this LAMS report was not edited by the Technical Information staff.

Printed in the United States of America. Available from
National Technical Information Service
U. S. Department of Commerce
5285 Port Royal Road
Springfield, Virginia 22151
Price: Printed Copy \$4.00; Microfiche \$0.95

LA-5320-MS
Informal Report
UC-4

ISSUED: July 1973

Hydrogen Absorption by AB_5 Compounds

by

J. L. Anderson
T. C. Wallace
A. L. Bowman
C. L. Radosevich
M. L. Courtney

NOTICE

This report was prepared as an account of work sponsored by the United States Government. Neither the United States nor the United States Atomic Energy Commission, nor any of their employees, nor any of their contractors, subcontractors, or their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness or usefulness of any information, apparatus, product or process disclosed, or represents that its use would not infringe privately owned rights.

MASTER

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

HYDROGEN ABSORPTION BY AB_5 COMPOUNDS

by

J. L. Anderson, T. C. Wallace, A. L. Bowman
C. L. Radosovich and M. L. Courtney

ABSTRACT

A study of hydrogen absorption-desorption by the intermetallic AB_5 compounds, where A = a rare earth and B = cobalt or nickel, has been undertaken. These compounds will readily absorb large quantities of hydrogen at ambient temperature and at pressures only slightly above the equilibrium dissociation pressures. When the hydrogen pressure over these hydrides is reduced below the dissociation pressure the hydrogen is rapidly and quantitatively desorbed.

It has been shown that the dissociation pressure for the AB_5 compounds increase as A changes across the lanthanide series (La-Gd). The total amount of hydrogen absorbed decreases as A is changed across the series. The nickel compounds generally absorb more hydrogen than the cobalt analog but the cobalt compounds have a lower dissociation pressure. By selectively changing A and B, hydrides with dissociation pressures from ~ 1.5 atm to ~ 130 atm can be synthesized. These compounds show considerable promise for use in the storage, transport and pumping of hydrogen.

I. INTRODUCTION

In 1969 Zijlstra and Westendorp¹ reported that the hexagonal compound $SmCo_5$ would absorb up to 2.5 atoms of hydrogen at a pressure of ~ 20 atmospheres at room temperature, transforming to an orthorhombic structure in the process. When the hydrogen pressure was reduced, the absorbed hydrogen was quickly and quantitatively desorbed by the material. The $SmCo_5$ is a member of a general family of AB_5 compounds, where A = a rare earth and B = Co or Ni. These compounds crystallize in the hexagonal $CaCu_5$ (space group $P6_3/mmm$) structure. Following this initial report, van Vucht et al.² initiated a study of hydrogen absorption by $LaNi_5$, $SmCo_5$ and $La_{1-x}Ce_xNi_5$. They showed that these compounds will indeed absorb large quantities of hydrogen at modest pressures and room temperature and that the compounds readily desorb the hydrogen at room temperature when the pressure is reduced. These compounds typically undergo some expansion of the unit cell when hydrided, but only the $SmCo_5$ appears to undergo a transformation

from the hexagonal symmetry. Shortly after this report Kuijpers and van Mal³ reported that there is a sorption hysteresis in the $LaNi_5 + H_2$ and $SmCo_5 + H_2$ systems. They demonstrated that in the two phase region of these systems there is a definite hysteresis with the desorption isotherm occurring at a lower pressure than the absorption isotherm. They stated that the magnitude of the hysteresis can be related to the volume expansion which accompanies the formation of the hydride.

The fact that these materials will absorb large quantities of hydrogen and quantitatively desorb the hydrogen rapidly at room temperature makes these systems quite interesting. It has been reported by van Vucht et al.² that $LaNi_5$ will absorb 6.7 atoms of hydrogen at a pressure of ~ 2.5 atmospheres. The reported hydrogen density for this material is 7.6×10^{22} atoms/cm³, or nearly twice as high as in liquid hydrogen. A hydrogen density of this magnitude is not in itself unique. For instance, the hydrogen densities, in H atoms per cm³ listed below are all

higher than the AB_5H_x compounds, $TiH_2 = 8.9 \times 10^{22}$, $VH_2 = 10.3 \times 10^{22}$, $UH_3 = 8.17 \times 10^{22}$ and $HfH_2 = 8.74 \times 10^{22}$. These compounds, however, require high temperature treatment to hydride-dehydride. The big advantage of the AB_5H_x compounds is the extreme ease of absorption-desorption at ambient temperature. This makes them very attractive as possible solid-storage devices for hydrogen isotopes.

II. EXPERIMENTAL

The intermetallic materials used in this study were prepared by arc melting the pure metals under argon. The "button" resulting from this procedure was crushed and a powder sample was prepared for x-ray diffraction. The powder pattern was taken using a Debye-Scherrer camera. A sample of the crushed material was placed in the hydriding apparatus and initially hydrided-dehydrided several times under relatively high (~ 100 atmospheres) hydrogen pressure. The apparatus used in this study was an all metal system utilizing Autoclave high pressure tubing and valves. A schematic of the apparatus is shown in Fig. 1. All volumes in the system were calibrated

Fig. 1. Schematic of experimental apparatus.

so gas volumes could be accurately determined. A 0-1000 psi Heise gauge was included in the apparatus but was used only as a coarse pressure indicator. Accurate pressure measurements were made with calibrated strain gauge pressure transducers. The output from the transducers was fed to a digital voltmeter and recorded on a Brown strip chart recorder. The H_2 used was of a nominal 99.9% purity and was used without any purification treatment. An analysis of this gas showed it to contain ~ 50 ppm argon and ~ 100 ppm carbon monoxide. On occasion a high

pressure experiment would require gas of a higher pressure than available in commercial tanks. For these tests a special tank of high pressure (10,000 psi) hydrogen was obtained from Group W-7, LASL. This gas was also used without any treatment. For runs at temperatures other than ambient an oil bath was placed around the reaction vessel. The temperature of the bath was maintained constant to $\pm 0.5^\circ C$.

The initial preparation of the sample involved crushing the arc melted material so the largest particles were $\sim 3/16$ in. maximum dimension. This material was then hydrided and dehydrided several times at ~ 100 atmospheres hydrogen pressure. This activation step resulted in the breaking up of the large particles into a fine powder, exposing fresh surface area. After several hydriding-dehydriding cycles the particle-size, as indicated by screen analysis, seemed to reach an equilibrium distribution. A typical screen analysis on activated $LaNi_5$ showed all of the material to be < 44 microns maximum dimension. If this powder was subsequently exposed to air it was then necessary to reactivate at the higher pressure. This tends to substantiate the idea that an oxide layer on the surface of the AB_5 will hinder the hydrogen absorption. Once the sample was activated the absorption-desorption isotherms could be accurately followed by the incremental addition or removal of known amounts of hydrogen. After each addition or removal the system was allowed to come to equilibrium and all necessary data recorded prior to any subsequent changes.

III. RESULTS AND DISCUSSION

An initial survey of the hydrogen absorption by AB_5 compounds has been completed. The compounds studied and the results obtained are summarized in Table 1. As one changes A across the lanthanide series (La-Gd) the resulting AB_5H_x compound becomes less stable, as indicated by the increased dissociation pressure and the lower total amount of hydrogen absorbed. If one, however, keeps A constant and looks at the effect of changing B from Ni to Co the results show a definite trend, but are not as readily explained. The Ni compounds generally absorb more hydrogen but the Co analogs have a lower equilibrium dissociation pressure. The one exception to these general rules is $LaCo_5$. This material absorbed hydrogen to form $LaCo_5H_{13.88}$. The absorption-desorption

Table I
Characteristics of AB₅ + H₂ Systems at 23°C

Sample	Initial Lattice Parameters, Å a_0 c_0	Max Com- position at 130 atm.	Plateau Pressure, atm.
LaNi ₅	5.020(1) 3.981(1)	LaNi ₅ H _{7.8}	1.90
LaNi ₅ + D ₂	5.020(1) 3.981(1)	LaNi ₅ D ₇	1.80
PrNi ₅	4.960(5) 3.979(4)	PrNi ₅ H _{8.93}	8
NdNi ₅	4.957(1) 3.971(1)	NdNi ₅ H _{8.97}	13
SmNi ₅	4.933(1) 3.965(1)	SmNi ₅ H _{8.95}	30
GdNi ₅	4.911(1) 3.966(1)	GdNi ₅ H _{8.9}	120
Y _{0.8} Th _{0.2} Ni ₅	4.920(1) 3.984(1)	No Reaction	---
La _{0.8} Th _{0.2} Ni ₅	5.014(2) 3.994(2)	No La _{0.8} Th _{0.2} Ni ₅ H _{8.5}	Plateau
YbNi ₅	4.855(3) 3.965(1)	YbNi ₅ H _{8.9}	~ 120
SmCo ₅	4.978(1) 3.987(1)	SmCo ₅ H _{2.58}	4.2
SmCo ₅ + D ₂	4.978(1) 3.987(1)	SmCo ₅ D _{2.5}	4.15
LaCo ₅	5.110(2) 3.970(1)	LaCo ₅ H _{3.83}	1.8 & lower
YCo ₅	4.952(3) 3.975(2)	YCo ₅ H _{3.8}	3-8
YNi ₅	4.892(1) 3.960(1)	YNi ₅ H _{4.4}	12
LaPt ₅	5.386(1) 4.378(2)	LaPt ₅ H _{2.3}	~ 130
SmFe ₅	No Reaction		

isotherm for this material had two plateaus, indicating two different hydrides present in the system. One plateau, at < 0.4 atmosphere corresponds to a material with a maximum composition of LaCo₅H_{2.9}. A second plateau at ~ 1.8 atmospheres corresponds to a material with a maximum composition of LaCo₅H_{2.68}.

Both LaNi₅ and SmCo₅ have been reacted with deuterium. These reactions proceed to form LaNi₅D₇ and SmCo₅D_{2.9} respectively. The deuterides have a dissociation pressure that is slightly lower than that measured for the corresponding hydride. This reversal of the expected isotope effect has been confirmed by Wiswall and Reilly.⁴

All of these AB₅ compounds are hexagonal structures with the CaCu₅-type structure, space group P6₃/mm, with c/a ~ 0.8. On hydriding these compounds there is an expansion of the cell, normally about a 20-25% expansion. The exact percentage expansion is difficult to determine, as we do not have facilities for taking x-ray data under hydrogen pressure. The material resulting from several absorption-desorption cycles has been x-rayed and shows some line broadening and some net expansion but due to the line broadening it is difficult to get good lattice parameters. van Vucht et al.² have shown that the LaNi₅ suffers

some 25% expansion on hydriding. They also report that SmCo₅ undergoes a transformation to an orthorhombic structure with a net cell expansion of 10%. They state that in general the RNi₅ compounds show an isotropic expansion preserving the hexagonal geometry while the RCo₅ compounds generally show an anisotropic expansion destroying the hexagonal structure.

A neutron diffraction study⁵ on LaNi₅D₇ was undertaken to measure the actual cell expansion on hydriding. It was also hoped that the actual hydrogen position could be identified by this technique. A sample of activated LaNi₅ was loaded in a 0.9 cm i.d. and 1.5 cm o.d. cylindrical stainless steel reaction tube. The system was pressurized at 12 atmospheres of deuterium and used directly for the neutron diffraction experiment. The calculated composition, based on the measured pressure-composition isotherm was LaNi₅D_{8.81}.

Neutron-diffraction data were obtained at the Los Alamos Omega West Reactor, scanning from 2θ=10 to 60° at angle intervals of 0.1° at a wave-length of 1.1422 Å. The sample was in the form of a vertical cylinder smaller than the neutron beam. The diffraction pattern is shown in Fig. 2. The very strong peaks are from the steel pressure vessel. Observed intensities were obtained by fitting the diffraction data to the equation

$$y = B(x) + \sum_n \left\{ \frac{I_n}{a_n \sqrt{2\pi}} \exp\left[-\frac{1}{2a_n^2}(x-b_n)^2\right] \right\}$$

by the least squares, where y is the number of diffracted neutrons at the Bragg angle x/2 and I_n, a_n and b_n are the intensities, peak width, and mean

Fig. 2. Neutron diffraction pattern for LaNi₅D₇.

value of 2 θ of the nth peak, and B(x) is a linear background function.

The observed neutron diffraction pattern of $\text{LaNi}_5\text{D}_{8.8}$ can be indexed on a hexagonal unit cell, with $a_0 = 5.387(1)$, $c_0 = 4.273(1)$. This compares with lattice parameters of $a_0 = 5.020(1)$, $c_0 = 3.980(1)$ for the LaNi_5 starting material. Thus the hydriding of LaNi_5 resulted in a volume expansion of 24%, with no other change in the unit cell.

The unit cell of LaNi_5 is shown in Fig. 3 in the projection perpendicular to the c-axis. The structure is defined as hexagonal, space group $P6_3/mmm$, La in 1(a)(000), Ni_I in 2(c)(1/3 2/3 0), Ni_{II} in 3(g)(1/2 0 1/2). There exist in this structure two sets of tetrahedral holes, which should be the most favored sites for the deuterium atoms. These are designated in Fig. 3 as H_I in 12(o)(x2x2), $x \sim 0.21$, $z \sim 0.29$ and H_{II} in 12(n)(x0z), $x \sim 0.43$, $z \sim 0.12$. These holes, coordinated by a LaNi_3 tetrahedron, have a radius of $\sim 0.31\text{\AA}$ in the metallic compound, assuming $r_{\text{La}} = 1.88$ and $r_{\text{Ni}} = 1.25\text{\AA}$. The first approximation for LaNi_5D_7 would place the seven D-atoms in these 24 sites. However, the possible hydrogen sites are so located that a random occupation does not appear to be possible. The H_{II} sites are in three clusters of four sites each, with H-H distances of 0.7 to 1.1 $\text{\AA}$ within the clusters. These short distances would seem to preclude the filling of more than one site per cluster up to a maximum of

three H_{II} atoms. The minimum H_I - H_{II} distance of 1.3 $\text{\AA}$ also places a restriction on the filling of H_I sites after an H_{II} site has been filled. Thus the requirement of a minimum H-H distance of 1.5 $\text{\AA}$ reduces the number of available sites to nine, all of which are defined by the filling of one site with a hydrogen atom. These considerations lead to an ordered arrangement, which is defined by space group $P31m$, with La in 1(a)(000), Ni_I in 2(b)(1/3 2/3 z) $z \sim 0$, Ni_{II} in 3(c)(x0z) $x \sim 1/2$, $z \sim 1/2$, H_I in 6(d)(xyz) $x \sim 0.21$, $y \sim 0.79$, $z \sim 0.71$, H_{II} in 3(c) $x \sim 0.43$, $z \sim 0.12$.

The best agreement between observed and calculated intensities was obtained with the ordered model, space group $P31m$, with coordinates for Ni_I , $z = 0.95$, Ni_{II} , $x = 0.50$, $z = 0.48$; H_I , $x = 0.25$, $y = 0.86$, $z = 0.58$; H_{II} , $x = 0.50$, $z = 0.08$; with 3.8 H_I and 3.0 H_{II} .

The uncertainties of this solution are so large that the results must be considered as qualitative. It appears certain, however, that the LaNi_5 lattice is slightly distorted, with a partially ordered filling of the possible hydrogen sites. There is one hydrogen in each of the three clusters of H_{II} sites. The calculations are based on an atom in the center of the cluster, but the atoms may occupy at random two of the four sites (the two with $z > 0$). The other 3.8 deuterium atoms are distributed randomly over the six H_I sites with $z > 1/2$. It seems possible that the structure for $\text{LaNi}_5\text{D}_{8.8}$ at 23°C may represent an intermediate state between a completely random hydride at elevated temperatures and a completely ordered compound existing at lower temperatures.

In all of the systems studied to date there is a sorption hysteresis in the pressure-composition isotherms. As the reaction temperature is increased the absolute magnitude of the hysteresis is increased. Once the samples have been activated the absorption-desorption isotherms are quite reproducible, with the hysteresis remaining well defined. Fig. 4 shows the measured isotherms of LaNi_5 , demonstrating the very marked hysteresis seen in this system.

The equilibrium dissociation pressures for SmCo_5 , LaNi_5 , PrNi_5 and NdNi_5 were measured at 23°C, 52°C and 72°C. Figs. 5-8 are plots of the log of the measured dissociation pressure vs $1/T$ for these systems. It is interesting to note that the four

Fig. 3. Unit cell of LaNi_5 (projection perpendicular to c-axis), showing most probable hydrogen sites.

Fig. 4. Absorption-desorption isotherm for LaNi_5H_2 .

curves have essentially the same slope. These curves can be defined by the general equation $\log P = -A/T + B$. When plotting these curves the equilibrium dissociation pressure used was that measured on the desorption of hydrogen. This was chosen because of the observed hysteresis in the absorption-desorption isotherms. The desorption isotherms remained fairly constant and reproducible whereas the absorption isotherms varied significantly during

Fig. 5. Temperature dependence of dissociation pressure for LaNi_5/H_2 system.

Fig. 6. Temperature dependence of dissociation pressure for SmCo_5/H_2 system.

the activating process. Table II is a tabulation of the data including the relative partial molal enthalpies and entropies for the reactions.

As the temperature of the reaction is increased, not only does the equilibrium pressure increase but also the total amount of hydrogen absorbed by the

Table II

Temperature Effects on Hydrogen
Absorption by AB₅ Compounds

Compound	A	B	ΔH , kcal	ΔS , eu
SmCo ₅	1583	5.98	-7.24±0.20	-27.36±0.10
LaNi ₅	1587	5.60	-7.26±0.20	-25.62±0.10
PrNi ₅	1593	6.27	-7.29±0.20	-28.69±0.10
NdNi ₅	1539	6.27	-7.04±0.30	-28.69±0.15

constant ΔH for these reactions indicates that the hydriding reaction is essentially the same in these four systems and presumably the same in all AB₅+H₂ systems. The reaction probably proceeds through the dissociation of H₂ molecules, on the AB₅ surface, to form H atoms which then diffuse through the material to an active site where the reaction takes place.

van Vucht et al.² reported a hydrogen density of 7.6×10^{22} hydrogen atoms/cm³ in the LaNi₅+H₂ system. The results of our experiments confirm a hydrogen density of $\sim 7 \times 10^{22}$ atoms/cm³ in LaNi₅H_{7.8}. This number is based on a 2% expansion of the LaNi₅ cell when hydrided. The LaNi₅H_{7.8} system has the highest hydrogen density of the AB₅+H₂ systems. As we have not measured the cell expansion during hydriding of other AB₅ systems we cannot calculate an accurate hydrogen density. All other AB₅ systems do, however, absorb considerably less hydrogen than the LaNi₅.

We have also found that foreign gases in the hydrogen are very effective in "blocking" the hydrogen reaction. As little as 0.5 volume % He in H₂ has been found to be quite effective in slowing down the hydriding reaction. Whereas hydrogen will normally react with activated LaNi₅ within a minute to form LaNi₅H₇, the addition of this 0.5% He slows the reaction such that ~ 6 hours are required to reach a composition of only LaNi₅H₆. When a 50 volume % H₂-He mixture was used the reaction formed LaNi₅H₄ over a three day period. It was shown that N₂ and Ar are equally effective in blocking the hydrogen reaction. We suggest that the foreign gas fills the pores around the powdered intermetallic material, blocking out the hydrogen. The rate controlling step is then the gas phase diffusion of hydrogen through the inert gas. This is apparently not a poisoning effect, as once the foreign gas is pumped out the hydrogen will react rapidly without any further activation of the material.

Fig. 7. Temperature dependence of dissociation pressure for PrNi₅/H₂ system.

Fig. 8. Temperature dependence of dissociation pressure for NdNi₅/H₂ system.

compound decreases. This can easily be seen in the LaNi₅H_x isotherms of Figure 4. The essentially

In order to assess the influence of the La/Ni atom ratio on hydrogen absorption a series of materials in the La-Ni system have been examined in some detail. Compositions from LaNi₁ to LaNi_{1.5} have been prepared by arc-melting and the phases present identified by x-ray powder pattern analysis. Tables III and IV list the materials studied and the phases found to exist in these materials. A sample of LaPt was also investigated. The study of this material was prompted by the unexpected results found for LaNi₁. Materials in the range LaNi_{1.0} to LaNi_{1.5} were single phased and formed hydrides with hydrogen contents ~ 3.5 atoms H per intermetallic molecule. These hydrides, including the LaPtH_{2.8} were stable down to pressures of ~ 3 x 10⁻⁷ torr. Even though this material formed a stable hydride, the hydrided species was extremely reactive in air. These materials generally absorbed less hydrogen with increasing Ni content.

For the materials with compositions LaNi_{4.76} to LaNi_{1.5} there were some definite trends measured. These materials containing an excess of Ni were two phased materials, containing LaNi₅ plus free Ni. For compositions up to LaNi_{1.2} the material will react to form LaNi₅H₇ plus free Ni. As the amount of excess Ni increases the difficulty of activating the material likewise increases. Once activated, however, hydrogen can readily be absorbed-desorbed from these materials. At a composition of LaNi_{1.5} the hydrogen absorption characteristics drop off quite dramatically. Presumably this is due to the large excess of Ni coating the LaNi₅ and preventing hydrogen from reaching the surface of the LaNi₅. As the

Table III

Reaction of LaNi_x Alloys with H₂ 25°C

Composition	Hydride Composition*	Phases Identified by X-ray Analysis
LaNi _{4.76}	LaNi ₅ H _{8.2}	LaNi ₅ , LaNi ₂
LaNi ₆	LaNi ₅ H _{7.4}	LaNi ₅ , Ni
LaNi ₇	LaNi ₅ H _{7.2}	LaNi ₅ , Ni
LaNi ₈	LaNi ₅ H ₈	LaNi ₅ , Ni
LaNi ₉	LaNi ₅ H _{7.3}	LaNi ₅ , Ni
LaNi ₁₀	LaNi ₅ H _{7.5}	LaNi ₅ , Ni
LaNi ₁₁	LaNi ₅ H ₈	LaNi ₅ , Ni
LaNi ₁₂	LaNi ₅ H ₈	LaNi ₅ , Ni
LaNi ₁₅	LaNi ₅ H _{10.7}	LaNi ₅ , Ni

*Composition calculated on amount of LaNi₅ present in LaNi_x sample.

Table IV

Reaction of Hydrogen with LaNi_{1.0} - LaNi_{2.0} Alloys

Composition	Phases Present	Composition of Stable Hydride
LaNi _{1.0}	LaNi ₁	LaNiH _{4.1}
LaNi _{1.1}	LaNi ₁ , LaNi ₂ , LaNi ₅ + unidentified	LaNi _{1.1} H _{3.2}
LaNi _{1.2}	" " " "	LaNi _{1.2} H _{3.3}
LaNi _{1.5}	" " " "	LaNi _{1.5} H _{3.0}
LaNi _{2.0}	" " " "	LaNi ₂ H _{2.5}
LaPt _{1.0}	Single Phased	LaPt ₁ H _{2.8}

composition approaches LaNi₅ the material no longer spalls during the hydriding. The Ni matrix is now able to provide some physical integrity to the material without being present in such excess to block the hydride formation.

IV. CONCLUSIONS

The results of these studies indicate that the AB₅ compounds will indeed absorb large quantities, but not especially unique quantities, of hydrogen. They are indeed unique in the ease of absorption and desorption of such quantities of hydrogen. These compounds will generally not be useful for hydrogen gettering as in all cases the dissociation pressure is too high for an effective getter.

There does seem to be some real possibility of using the AB₅ compounds for the storage and transport of hydrogen. The extreme ease and rapidity of hydrogen absorption and desorption at ambient temperatures make them unique among hydrogen compounds. As society looks more closely at hydrogen as a fuel to help relieve the impending energy crisis, these materials will undoubtedly be considered for many applications. A careful choice of A and B can provide a hydrogen source for a wide range of pressures.

ACKNOWLEDGMENTS

We are pleased to acknowledge the help of Mr. Conrado P. Gutierrez for the initial design and construction of the apparatus used in this study. He also performed several of the initial experiments. We are especially grateful to Drs. J. D. Farr and U. T. Vier for their suggestions and helpful discussions related to this study.

REFERENCES

1. H. Zijlstra and F. F. Westendorp, "Influences of Hydrogen on the Magnetic Properties of SmCo_5 ," Solid State Comm. 7, 857 (1969).
2. J. H. N. van Vucht, F. A. Kuijpers and C. A. M. Bruning, "Reversible Room-Temperature Absorption of Large Quantities of Hydrogen by Intermetallic Compounds," Philips Res. Rpts. 25, 133 (1970).
3. F. A. Kuijpers and H. H. van Mal, "Sorption Hysteresis in the $\text{LaNi}_5\text{-H}$ and $\text{SmCo}_5\text{-H}$ Systems," J. Less-Common Metals 23, 395 (1971).
4. R. H. Wiswall, Jr. and J. J. Reilly, "Inverse Hydrogen Isotope Effects in Some Metal Hydride Systems," Inorg. Chem. 11, 1691 (1972).
5. A. L. Bowman, J. L. Anderson and N. G. Nereson, "A Neutron Diffraction Study of LaNi_5D_7 ," to be published in Proc. of 10th Rare Earth Research Conf., Carefree, Arizona, April 30-May 3, 1973.