BNWL-414
2-

AEC
RESEARCH
and
DEVELOPMENT
REPORT

**QUARTERLY PROGRESS REPORT
A STUDY OF TUNGSTEN-TECHNETIUM ALLOYS
APRIL 1, 1966-OCTOBER 1, 1966**

**R. S. KEMPER
D. P. O'KEEFE**

APRIL 1967

DATE	FROM	TO	REMARKS
APR 11 1966	W. E. Greenhalgh	2912	325
MAY 1 1966	Director	60013	2714
MAY 21 1966	J. S. Cochran	60009	703

BATTELLE-NORTHWEST

BATTELLE MEMORIAL INSTITUTE / PACIFIC NORTHWEST LABORATORY

LEGAL NOTICE

This report was prepared as an account of Government sponsored work. Neither the United States, nor the Commission, nor any person acting on behalf of the Commission:

A. Makes any warranty or representation, expressed or implied, with respect to the accuracy, completeness, or usefulness of the information contained in this report, or that the use of any information, apparatus, method, or process disclosed in this report may not infringe privately owned rights; or

B. Assumes any liabilities with respect to the use of, or for damages resulting from the use of any information, apparatus, method, or process disclosed in this report.

As used in the above, "person acting on behalf of the Commission" includes any employee or contractor of the Commission, or employee of such contractor, to the extent that such employee or contractor of the Commission, or employee of such contractor prepares, disseminates, or provides access to, any information pursuant to his employment or contract with the Commission, or his employment with such contractor.

PACIFIC NORTHWEST LABORATORY

RICHLAND, WASHINGTON

operated by

BATTELLE MEMORIAL INSTITUTE

for the

UNITED STATES ATOMIC ENERGY COMMISSION UNDER CONTRACT AT(45-1)-1830

PRINTED BY/FOR THE U. S. ATOMIC ENERGY COMMISSION

3 3679 00060 5685

BNWL-414
UC-25, Metals, Ceramics
and Materials

QUARTERLY PROGRESS REPORT
A STUDY OF TUNGSTEN-TECHNETIUM ALLOYS
APRIL 1, 1966-OCTOBER 1, 1966

By

R. S. Kemper
D. P. O'Keefe

Metallurgy Department

April 1967

**FIRST UNRESTRICTED
DISTRIBUTION MADE** MAY 2 '67

Sponsored by the National Aeronautics and Space Administration
Project Management at Washington, D. C.

J. W. Maltz, Office of Advanced Research and Technology

PACIFIC NORTHWEST LABORATORY
RICHLAND, WASHINGTON

Printed in the United States of America
Available from
Clearinghouse for Federal Scientific and Technical Information
National Bureau of Standards, U.S. Department of Commerce
Springfield, Virginia 22151
Price: Printed Copy \$3.00; Microfiche \$0.65

Previous Quarterly Progress Reports in this series:

HW-83550	April 1, 1964-July 1, 1964
HW-84309	July 1, 1964-October 1, 1964
HW-84550	October 1, 1964-January 1, 1965
BNWL-141	January 1, 1965-April 1, 1965
BNWL-142	April 1, 1965-July 1, 1965
BNWL-162	July 1, 1965-October 1, 1965
BNWL-196	October 1, 1965-January 1, 1966
BNWL-378	January 1, 1966-April 1, 1966

QUARTERLY PROGRESS REPORT
A STUDY OF TUNGSTEN-TECHNETIUM ALLOYS
APRIL 1, 1966-OCTOBER 1, 1966

R. S. Kemper
D. P. O'Keefe

INTRODUCTION

Technetium is a sister element to rhenium and has many properties that are similar to rhenium. It is predicted that technetium will have about the same effects on tungsten as rhenium in regard to increase in workability, lowered ductile-to-brittle transition temperature, and improved ductility.

The objectives of the current work are to recover technetium from fission product wastes at Hanford and reduce to purified metal; prepare W-Tc alloys containing up to 50 at.% Tc; fabricate the alloy ingots to sheet stock, assessing the effect of technetium on workability; and perform metallurgical and mechanical property evaluation of the fabricated alloys.

Previous reports have described the separation and purification of 800 g of technetium metal powder, melting of technetium and W-Tc alloys and some properties of the arc cast alloys.

CURRENT PROGRESS

During the two quarters, the electron beam remelted alloys were forged while encapsulated in molybdenum cans; the protective can stock was removed chemically and examination was made of the material.

The buttons were individually sealed in molybdenum cans 1 1/2 in. OD x 1 1/8 in. ID x 3/4 in. overall height by electron beam welding. The end caps were 1/16 in. thick molybdenum.

To heat for forging, the cans were placed in a molybdenum block in an induction coil in flowing argon. A forging temperature of 1675 to 1700 °C was selected for all the alloys. Temperatures were monitored by a W-W/Re thermocouple between the block and can, and a L&N optical pyrometer sighted on the can surface. The cans were placed on anvils in a 700 ton vertical hydraulic press and forged to 0.275 to 0.300 in. thickness in one press.

The 50 and 60 at.% Tc alloys fractured badly and penetrated the molybdenum can surface and caused some contamination problem. Small particles of the 60 at.% alloy were hard enough to be imbedded in the press anvil. All the alloys were chemically decladded by using an acid bath of H_2O , HNO_3 , and H_2SO_4 . All the alloys were reduced by forging to 0.120 to 0.160 in. thickness except for one of the 10 at.% Tc alloys that was forged to 0.215 in. thickness. The surface appearance of the as-forged alloys is shown in Figures 1 through 16. The molybdenum was softer than the alloys at forging temperature which produced surface roughening on the forgings related to their grain size. The effect of technetium in reducing grain size is quite pronounced. It is interesting to note that approximately equivalent atomic percent technetium additions are required to produce the grain size effect observed in the W-Re alloy. Edge cracking was noted in alloys of 20 at.% Tc or greater, with the severity increasing with increasing technetium content. Severe breakup occurred in both the 50 and 60 at.% Tc alloys that previously had been identified as two phase alpha solid solution plus sigma. These forging results for the intermediate solid solution alloys are encouraging, and preparations are being made to further reduce the alloys by hot rolling to sheet of 0.050 in. or less thickness.

Neg 566-5186

5X

FIGURE 1. Tungsten as Forged; Approximately 60%
Reduction - 1700 °C.

Neg 566-5180

5X

FIGURE 2. *W-25 at.% Re as Forged; Approximately 60%
Reduction - 1700 °C.*

Neg. 566-5181

5X

FIGURE 3. W-2.5 at.% Tc as Forged; Approximately 60% Reduction - 1700 °C.

Neg 566-5182

5X

FIGURE 4. W-3.5 at.% Te as Forged; Approximately 60% Reduction - 1700 °C.

Neg 566-5183

5X

FIGURE 5. W-5 at.% Tc as Forged; Approximately 60% Reduction 1700 °C.

Neg 566-5184

5X

FIGURE 6. W-5 at.% Tc as Forged; Approximately 60%
Reduction - 1700 °C.

Neg 566-5188

5X

FIGURE 7. *W-10 at.% Tc as Forged; Approximately 40%
Reduction - 1700 °C.*

Neg 566-5187

5X

FIGURE 8. W-10 at.% Tc as Forged; Approximately 60%
Reduction - 1700 °C.

Neg 566-5188

5X

FIGURE 9. *W-20 at.% Tc as Forged; Approximately 60%
Reduction - 1700 °C.*

Neg 566-5189

5X

FIGURE 10. *W-20 at.% Tc as Forged; Approximately 60% Reduction - 1700 °C.*

Neg 566-5190

5X

FIGURE 11. *W-30 at.% Tc as Forged; Approximately 60%
Reduction - 1700 °C.*

Neg 566-5191

5X

FIGURE 12. *W-30 at.% Tc as Forged; Approximately 60%
Reduction - 1700 °C*

Neg 566-5192

5X

FIGURE 13. W-40 at.% Tc as Forged; Approximately 60% Reduction - 1700 °C.

Neg 566-5193

5X

FIGURE 14. *W-40 at.% Tc as Forged; Approximately 60% Reduction - 1700 °C.*

Neg 566-5194

5X

FIGURE 15. *W-50 at.% Tc as Forged.*

Neg 566-5185

5X

FIGURE 16. *W-60 at.% Te as Forged.*

DISTRIBUTIONNo. of
Copies

1	<u>Army Materials Research Agency</u> S. V. Arnold
3	<u>Atomic Energy Commission, Richland</u> Division of Reactor Development and Technology P. G. Holsted
2	<u>Atomic Energy Commission, Washington</u> Division of Reactor Development and Technology K. Horton
2	<u>Battelle Memorial Institute</u> Defense Metals Information Center R. I. Jaffee
3	<u>Bureau of Mines</u> Department of Interior Washington, D.C. R. F. Stevens, Jr., (Commodity Specialist)
1	<u>Bureau of Naval Weapons</u> Department of Navy Washington, D.C. 20546 T. F. Kearns, (RRMA-2)
1	<u>Chicago Patent Group</u>
1	<u>Climax Molybdenum Company of Michigan</u> 14419 Woodrow Wilson Detroit 38, Michigan M. Semchyschen
326	<u>Division of Technical Information Extension</u>
1	<u>General Electric Company</u> Research Laboratory P. O. Box 1088 Schenectady, New York
4	<u>General Electric Company, Cincinnati</u> L. P. Jahnke (Advanced Engine Technology Dept.) J. A. McGurty E. D. Sayre, (APED) C. S. Wukusick

No. of
Copies

- 1 General Electric Company
Lamp Metal Component Department
Cleveland, Ohio
J. H. Keeler
- 1 General Electric Company, Richland
GETA File Copy
- 1 General Telephone and Electronics Laboratories, Inc.
Bayside 60, New York
L. L. Seigle
- 1 Jet Propulsion Laboratory
Engineering Mechanics Division
H. Martens
- 1 Lawrence Radiation Laboratory
J. Hadley
- 1 NASA Ames Research Center
Vehicle Environment Division
Charles A. Hermach
- 1 NASA Goddard Space Flight Center
Spacecraft Systems Division
H. E. Frankel
- 1 NASA Langley Research Center
Structures Research Division
E. E. Mathauser
- 2 NASA Lewis Research Center
W. D. Klopp, (105-1)
N. Saunders, M&S Div)
- 1 NASA Manned Spacecraft Center
R. L. Johnston, (S&M Div)
- 1 NASA Marshall Space Flight Center
W. R. Lucas, (R-P&VE-M)

No. of
Copies

2	<u>National Aeronautics and Space Administration</u> 600 Independence Avenue S.W. Washington, D.C. 20546 Joseph Maltz, (Code RRM)
2	<u>National Aeronautics and Space Administration</u> Universal North Building Washington, D.C. 20546 Office of Grants & Research Contracts, (Code SC)
3	<u>Richland Operations Office</u> C. L. Robinson R. K. Sharp Technical Information Library
1	<u>Union Carbide Corporation (ORNL)</u> Metals and Ceramics M. L. Picklesimer
1	<u>Universal-Cyclops Steel Corporation</u> Bridgeville, Pennsylvania C. P. Mueller
1	<u>Westinghouse Electric Corporation</u> Research Laboratory Churchill Boro Pittsburgh 35, Pennsylvania J. H. Bechtold
1	<u>Wright-Patterson Air Force Base</u> Dayton, Ohio Materials Laboratory K. Elbaum
32	<u>Battelle-Northwest</u> F. W. Albaugh S. H. Bush J. J. Cadwell D. R. de Halas L. A. Hartcorn R. N. Johnson R. S. Kemper

G. A. Last
J. E. Minor (10)
R. L. Moore
D. P. O'Keefe
F. P. Roberts
M. T. Walling
O. J. Wick (2)
F. W. Woodfield
Technical Information Files (5)
Technical Publications (2)