LEGAL NOTICE

This report was prepared as an account of Government sponsored work. Neither the United States, nor the Commission, nor any person acting on behalf of the Commission:

A. Makes any warranty or representation, expressed or implied, with respect to the accuracy, completeness, or usefulness of the information contained in this report, or that the use of any information, apparatus, method, or process disclosed in this report may not infringe privately owned rights; or

B. Assumes any liabilities with respect to the use of, or for damages resulting from the use of any information, apparatus, method, or process disclosed in this report.

As used in the above, "person acting on behalf of the Commission" includes any employee or contractor of the Commission, or employee of such contractor, to the extent that such employee or contractor of the Commission, or employee of such contractor prepares, disseminates, or provides access to, any information pursuant to his employment or contract with the Commission, or his employment with such contractor.

GEAP-4830
AEC Research and
Development Report
October, 1965

CFSTI PRICES

2.00
H.C. \$ ~~2.00~~ MN. 50

SODIUM MASS TRANSFER: XIV

STATISTICAL ANALYSIS OF 1961 TO 1964 SAMPLE WEIGHT CHANGE DATA

by

J. L. Jaech

E. L. Dunn

K. B. Stewart

RELEASED FOR ANNOUNCEMENT
IN NUCLEAR SCIENCE ABSTRACTS

Approved by

L. P. Bupp

L. P. Bupp, Manager
Vallecitos Atomic Laboratory

R. W. Lockhart

R. W. Lockhart, Project Engineer
Sodium Mass Transfer Program

E. L. Zebroski

E. L. Zebroski, Manager
Sodium Reactor Technology

Prepared for the
Sodium Components Development Program
of the
United States Atomic Energy Commission
Under Contract AT(04-3)-189
Project Agreement No. 15

Printed in U.S.A. Available from the
Clearing House for Federal Scientific and Technical Information
National Bureau of Standards, U.S. Department of Commerce
Springfield, Virginia
Price: ~~2.00~~ per copy
2.00

VALLECITOS ATOMIC LABORATORY
NUCLEAR TECHNOLOGY DEPARTMENT

GENERAL ELECTRIC
PLEASANTON, CALIFORNIA

This document is
PUBLICLY RELEASABLE

Benny Stale
Authorizing Official
Date: 1-23-07

LEGAL NOTICE

This report was prepared as an account of Government sponsored work. Neither the United States, nor the Commission, nor any person acting on behalf of the Commission:

- A. Makes any warranty or representation, expressed or implied, with respect to the accuracy, completeness, or usefulness of the information contained in this report, or that the use of any information, apparatus, method, or process disclosed in this report may not infringe privately owned rights; or*
- B. Assumes any liabilities with respect to the use of, or for damages resulting from the use of any information, apparatus, method, or process disclosed in this report.*

As used in the above, "person acting on behalf of the Commission" includes any employee or contractor of the Commission, or employee of such contractor, to the extent that such employee or contractor of the Commission, or employee of such contractor prepares, disseminates, or provides access to, any information pursuant to his employment or contract with the Commission, or his employment with such contractor.

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency Thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

DISCLAIMER

Portions of this document may be illegible in electronic image products. Images are produced from the best available original document.

TABLE OF CONTENTS

	<u>Page</u>
ABSTRACT	v
I. INTRODUCTION	-1-
II. CONCLUSIONS	-4-
III. SUMMARY OF RESULTS	-7-
IV. DERIVATION OF CORROSION RATE PREDICTION EQUATIONS	-13-
4.1 Method of Estimation	-13-
4.2 Hot Leg Equation	-14-
4.2.1 Time Effect	-14-
4.2.2 Effects of Secondary Variables	-14-
4.2.3 Effects of Primary Variables	-16-
4.2.4 Overall Hot Leg Prediction Equation	-17-
4.3 Cold Leg Equation	-21-
4.3.1 Time Effect	-21-
4.3.2 Effects of Secondary Variables	-21-
4.3.3 Effects of Primary Variables	-22-
4.3.4 Overall Cold Leg Prediction Equation	-22-
V. FURTHER DISCUSSION ON EACH VARIABLE	-28-
5.1 Time	-28-
5.2 Velocity	-28-
5.3 Temperature	-29-
5.4 Downstream	-29-
5.5 Oxygen	-29-
VI. APPENDIX	-30-
6.1 Carbon Correction	-30-
6.2 Data Transformation for Data Having the Wrong Sign	-30-
6.3 The Fractional Replicate Plan	-32-
6.4 Alternate Estimating Methods	-38-
LIST OF SODIUM MASS TRANSFER PROJECT REPORTS	-41-
DISTRIBUTION LIST	-43-

LIST OF ILLUSTRATIONS

<u>Figure</u>	<u>Title</u>	<u>Page</u>
1	Hot Leg Corrosion Rate Prediction Curves	-5-
2	Cold Leg Corrosion Rate Prediction Curves	-6-
3	Hot Leg Weight Loss Versus Time	-8-
4	Cold Leg Weight Gain Versus Time	-11-
5	Hot Leg Residuals	-19-
6	Between Run Hot Leg Variance	-20-
7	Residuals Versus Predicted Logarithm of Corrosion Rate	-25-
8	Between Run Variance	-26-
9	Hot Leg Average Run Residual Versus Corresponding Cold Leg Residual	-27-

LIST OF TABLES

<u>Table</u>	<u>Title</u>	<u>Page</u>
1	Definition of Run Type Test Conditions	-2-
2	Classification of Loop Runs	-2-
3	Typical Operating Conditions and Sample Location	-3-
4	Frequency Distribution of the Hot Leg Residuals	-18-
5	Cold Leg Temperature Coefficients	-21-
6	Frequency Distribution of the Cold Leg Residuals	-24-

ABSTRACT

Statistical methods are employed to analyze weight change data of Type-316 stainless steel, $2\frac{1}{4}$ Cr-1 Mo and 5 Cr- $\frac{1}{2}$ Mo- $\frac{1}{2}$ Ti alloy steel samples exposed to sodium in six forced convection test loops constructed of various combinations of the test materials. This report analyzes the data collected prior to the end of December, 1964.

The data are the results of a five-run fractional replicate test plan performed on the programs test loops. This plan was devised to evaluate the effects of loop maximum temperature; ΔT in the system, and oxygen impurity level. In addition to the effects of the above primary test variables, the effects of velocity, exposure time, sample temperature, and sample location in the test loop were evaluated. Multiple regression methods were used to evaluate these effects. The results are presented graphically and numerically to show the effects of the test variables on sample weight change, and to provide corrosion rate prediction equations.

EDITOR'S NOTE

This report presents the statistical methods used for analysis of corrosion data and its application to sample weight change data available through 1964. Results and analyses of other aspects of the information derived from the operation of the test loops and metallurgical effects are presented elsewhere in a series of reports listed at the end of the text.

FUNCTIONAL ORGANIZATION FOR PHASE I WORK OF THE SMT PROGRAM

Program Planning, Direction and Evaluation - Advance Engineering*
(K. P. Cohen, R. W. Lockhart)

Technical Consultants: L. E. Epstein, VAL, E. L. Zebroski, Advance Engineering*

Experimental Equipment Design and Operation - Advance Engineering*
(G. Billuris and L. E. Pohl)

Materials Examination - Fuels and Materials, VAL
(S. Naymark, R. S. Young, M. C. Rowland, D. E. Plumlee)

Statistical Analysis - Consulting Statistician, VAL
(D. Gaylor and J. L. Jaech)

Sodium Chemistry - Chemistry and Chemical Engineering, VAL
(D. H. Ahmann, W. Sabol, D. Dutina)

*Recently renamed Advanced Products Operation which is part of the Nuclear Energy Division of General Electric Company

SODIUM MASS TRANSFER: XIV

STATISTICAL ANALYSIS OF 1961-1964 SAMPLE WEIGHT CHANGE DATAI. INTRODUCTION

This is one in a series of reports* describing results obtained at the General Electric Company in the Sodium Mass Transfer Program sponsored by the U.S. Atomic Energy Commission. This program has generated data on the corrosion properties of various types of steel alloys in the region of anticipated operating conditions of sodium-cooled reactors. Statistical analyses of these data afford: (1) an understanding of the degree to which variables affect corrosion, (2) an opportunity to compare various corrosion prediction models for their ability to fit the data and their utility in prediction of corrosion rates, (3) an understanding of the variability in corrosion rates inherent under nominally the same operating conditions, and (4) the degree to which empirical models explain the variation. Additional benefits accrue from the observation of unanticipated results and the understanding which comes from relating observed results to those based on theoretical considerations.

This report presents the statistical analysis procedures and interpretation of the results for the sample weight-change data gathered to the end of 1964. Previous reports on the model development and analysis of the weight change data are included in GEAP-3726-V-1 "SMT II: Screening Test Data and Analysis - Mass Transfer Results" and in GEAP-4183 "SMT VI: Statistical Correlation of 1961 and 1962 Corrosion Data". This report involves the analysis of 2500 weight change data and completes the analysis of the five run fractional replicate test plan results.

The samples were exposed in one of six forced circulation loops designed and fabricated for the study of the mass transport phenomena in liquid sodium.⁽¹⁾ These loops were constructed of varying combinations of Type-316 stainless steel, $2\frac{1}{4}$ Cr-1 Mo and 5 Cr- $\frac{1}{2}$ Mo - $\frac{1}{2}$ Ti ferritic steel alloys as shown below:

<u>Loop</u>	<u>Material</u>		<u>Loop</u>	<u>Material</u>	
	<u>Hot Leg</u>	<u>Cold Leg</u>		<u>Hot Leg</u>	<u>Cold Leg</u>
No. 1	316 S. S.	316 S. S.	No. 4	316 S. S.	5 Cr
No. 2	316 S. S.	$2\frac{1}{4}$ Cr	No. 5	$2\frac{1}{4}$ Cr	$2\frac{1}{4}$ Cr
No. 3	316 S. S.	$2\frac{1}{4}$ Cr	No. 6	5 Cr	5 Cr

The operating conditions were varied between runs in the loops to determine the effects of the primary variables. These were: 1) the loop maximum temperature, 2) the system over-all temperature drop, and 3) the oxygen level in the sodium. Within each loop, samples were located in regions of different temperatures, velocities, and distances along the loop, and were removed at different exposure times. Such a pattern provided a secondary group of test variables - the within-run variables. The terms "primary" and "secondary" are not intended to indicate relative importance of these variables.

* The series of Program Topical Reports are listed at the end of this report.

(1) GEAP-3725 SMT I: Test Loop Design

The specific test plan conditions are indicated in Table 1. A discussion of the development of such a test plan is included in the Appendix (paragraph 6.3). The test runs operated under each test condition are listed in Table 2. Within Table 2 the first digit refers to the loop, while the second digit is the run number in that loop. For example, 3-7 is run Number 7 in Loop 3. Note that Loop 2 was not operated under the five run plan but was always operated under one test condition. Run Type D for Loop 1 was also not a part of the plan.

TABLE 1
DEFINITION OF RUN TYPE TEST CONDITIONS

<u>Run Type</u>	<u>Oxygen (PPM)</u>	<u>T_{max} (°F)*</u>	<u>ΔT(°F)**</u>
I	~50	1200	500
II	~12	1200	500
III	~12	1100	500
IV	~12	1200	250
V	~50	1100	250
D	~50	1300	500

* Maximum temperature in the loop

** Temperature differential in the system

TABLE 2
CLASSIFICATION OF LOOP RUNS

<u>Run Type</u>	<u>Loop 1</u>	<u>Loop 2</u>	<u>Loop 3</u>	<u>Loop 4</u>	<u>Loop 5</u>	<u>Loop 6</u>
I	1-1	—	3-1	4-1	5-1	6-1
II	1-2	2-1, 2-5	3-7	4-2	5-2	6-2
III	1-4	—	3-9	4-7	5-3	6-7
IV	1-3	—	3-8	4-5	5-4	6-6
V	1-5	—	3-10	4-6	5-5	6-5
D	1-1	—	—	—	—	—

The test conditions and sample locations in Table 3 are typical for the five run test plan. Within each run, the operating conditions for each sample location varied slightly. Detailed exposure data for each sample was reported in GEAP-3726-Vol 3, GEAP-4181, GEAP-4437 or GEAP-4836.

TABLE 3

TYPICAL OPERATING CONDITIONS AND SAMPLE LOCATIONHot Leg (Sodium being heated)

<u>Sample Position</u>	<u>Temperature (°F)</u>	<u>Velocity (fps)</u>	<u>Hydraulic Diameters* Downstream</u>	<u>No. of Samples</u>	<u>Sampling Plan **</u>
H1 in	999	7.4	50	3	7+ 21R, 14+ 4R, 28
H1 out	999	21.8	130	1	28
H2 in	1095	7.5	50	3	28, 28, 28
H2 out	1095	22.3	130	1	28
H3 in	1193	22.8	50	1	7+ 21R
H3 out	1193	22.8	130	1	14+ 14R
H3R in	1202	7.6	270	3	7+ 21R, 14+ 14R, 28
H3R out	1202	22.8	350	1	28

Cold Leg (Sodium being cooled)

C1 (out)	1098	7.6	50	3	7+ 21R, 14+ 14R, 28
C2 (out)	997	7.6	50	3	28, 28, 28
C3 in	701	7.6	50	3	7+ 21R, 14+ 14R, 28
C3 out	701	7.6	130	3	7+ 21R, 14+ 14R, 28

* Measured from the beginning of an isothermal region.

** The numbers shown are in hundreds of hours, and represent exposure times of samples removed. The designation (7+ 21R), for example, means the sample in this position was removed at 700 hours. Its replacement (designated by R), was exposed in the sample slot for 2100 hours.

Weight changes were measured with good precision. The corrosion samples were carefully weighed to the nearest 0.02 milligram before and after each run. After exposure, each sample was removed from the test loop, immersed in alcohol and allowed to stand until the chemical reaction stopped. If any solid corrosion products appeared in the alcohol, they were collected, dried, and weighed separately for each sample. The data were from hockey-stick-shaped corrosion samples with an area of approximately 0.09 square decimeters and weighing about 4000 milligrams. An analysis of successive weighings on unexposed samples showed that 95 percent of the readings fell within a limit of ± 0.06 milligram. This was well within the ± 0.1 milligram maximum limit set for the experiment and is extremely precise weighing. However, ± 0.06 milligram was a substantial portion of many of the weight changes resulting from the less severe run conditions. In this region, weighing errors contributed substantially to the variation between samples that were observed.

Because of the number and character of the variables, a multiple regression, least-squares curve fitting technique was used in the analysis. With the multiple-regression technique, the significance of the data, is increased since the evaluation of each effect makes use of all the data.

II. CONCLUSIONS

- (1) There are no significant differences in the corrosion rates of austenitic and ferritic alloys. All six loops exhibited similar corrosion rates.
- (2) The corrosion rate was more rapid during the early exposure of a sample. Steady state conditions were reached between 500 to 1000 hours.
- (3) The effects of the secondary, or within-run, variables of sodium temperature and velocity were significant as expected, and were estimated with good precision. This analysis confirms the previously reported effect that samples downstream from the beginning of an isothermal region were found to have significantly lower corrosion rates than preceding samples. This was labeled a "downstream" effect.
- (4) Of the primary variables in the fractional replicate test plan, only oxide level in the hot leg, and both oxide level and temperature drop in the cold leg, were found to affect corrosion rates significantly. Of course, the loops having higher maximum temperatures did exhibit the higher corrosion rates, but the extent to which they were higher was consistent with that predicted from the within-run temperature effect. Maximum loop temperature, as such, was therefore not a significant variable.
- (5) Corrosion rate prediction curves for the hot and cold legs are plotted in Figures 1 and 2. The corrosion rate prediction equations are presented in Section 3.

FIGURE 1 HOT LEG CORROSION RATE PREDICTION CURVES

FIGURE 2 COLD LEG CORROSION RATE PREDICTION CURVES

III. SUMMARY OF RESULTS

Results are summarized separately for the hot and cold legs. The "hot" and "cold" designations refer to portions of the loop in which the sodium was being heated or cooled respectively. Generally speaking, samples lost weight in the hot leg, and gained weight in the cold leg. In both the hot and cold leg no significant differences were observed between the six loops. Thus, loop composition, over the range studied here, was not a significant variable.

Hot leg results:

- (1) Samples were found to corrode at a faster rate during their early periods of exposure. The mathematical model used to describe this phenomenon implies that steady state conditions are never reached, except asymptotically. However, near-steady state is reached at about one month's exposure. This is shown in Figure 3 where weight loss versus exposure time is plotted for a typical sample. Steady state is obtained when this plot becomes linear.
- (2) On the average, an increase in local temperature of 100F gives rise to an increase in corrosion rate by the following factors:

<u>Temperature Increase</u>	<u>Corrosion Rate Increase</u>
900F to 1000F	Factor of 3.3
1000F to 1100F	Factor of 2.9
1100F to 1200F	Factor of 2.5

- (3) On the average, an increase in sodium velocity by a factor of 3, which represented the factor difference between low and high velocities in the loops, gave rise to an increase in corrosion rate by a factor of 2.7.
- (4) Originally it was not anticipated that the rate of corrosion of a sample would depend on its position downstream from the beginning of an isothermal region. However, this was found to be the case to a significant degree. The number of hydraulic diameters downstream was used as a convenient variable to describe this effect. At 50 such diameters downstream from the beginning of an isothermal region, the corrosion rate is 71 percent of what it is at the beginning of the region. At 350 diameters, the maximum observed, this drops to 9 percent on the average.
- (5) The level of oxygen in the sodium strongly affected the corrosion rate. A change in this level from 12 to 50 ppm, the two levels tested, resulted in a corrosion rate increase by a factor of 5.2.
- (6) Neither of the two remaining primary variables, $t_{\max}$ and ΔT , significantly affected the corrosion rate. Samples in the runs having higher maximum temperatures experienced greater weight losses by an amount consistent with that predicted from the local sample temperature effect, so the maximum loop temperature as such was not a significant variable.

FIGURE 3 HOT LEG WEIGHT LOSS VERSUS TIME

- (7) The residual error variation is made up of three components:

(a) Variance within a sample slot (σ_s^2)

(b) Variance between slots within a run (σ_w^2)

(c) Variance between runs (σ_b^2)

The analysis was performed on the natural logarithms of steady-state corrosion rates expressed in $\text{mg}/\text{dm}^2 \cdot \text{mo}$. For these transformed data, estimates of the variance components are as follows:

$$\sigma_s^2 = 0.076$$

$$\sigma_w^2 = 0.290$$

$$\sigma_b^2 = \underline{0.345}$$

$$\text{Total Variance} = 0.711$$

$$\text{Total Standard Deviation} = 0.84$$

$$95 \text{ percent limit: } 2 \text{ Standard Deviations} = 1.68 \text{ (Factor of 5.4)}$$

There is some lack of homogeneity in the variance. At the low corrosion rates, the data exhibit greater scatter than at the higher rates. Specifically at the low rates ($\ln R < 1$, or $R < 2.7 \text{ mg}/\text{dm}^2 \cdot \text{mo}$), the 95 percent confidence limit factor of uncertainty is ± 8.1 , while at the higher rates, it is ± 4.0 . The higher rates are, of course, those of greatest practical importance.

- (8) A hot leg corrosion rate prediction equation was developed as a function of the test variables. This equation is as follows:

$$\begin{aligned} \ln R_1 = & 12.845 + 0.884 \ln v - \left[\frac{23,827}{(T + 460)} \right] - 0.00676 (L/D) \\ & + 1.156 \ln Ox + \frac{2.26}{(t + 1)} \end{aligned}$$

where

R_1 = rate of weight loss to time t . ($\text{mg}/\text{dm}^2 \cdot \text{mo}$)

v = sodium velocity (fps)

T = sample temperature ($^{\circ}\text{F}$)

(L/D) = downstream factor = number of hydraulic diameters downstream in an isothermal region

t = months (700 hours) exposure

This equation gives the predicted corrosion rate from time zero to time t . Steady-state rates are found by letting $t \rightarrow \infty$ which is equivalent to dropping the term involving t from this equation. For one condition the solution of this equation is presented graphically in Figure 1.

Cold Leg Results:

- (1) As in the hot leg, there is an initial period of early exposure in which the sample gains weight faster. This effect was not as strong in the cold leg as in the hot leg and is shown graphically in Figure 4 for a typical sample.
- (2) The effect of an increase in local temperature was found to depend on temperature drop in the loop. This phenomenon is discussed in greater detail in Paragraph 4.3.4 of this report. The average effect of temperature may be described as follows:

	<u>Temperature Increase</u>	<u>Corrosion Rate Increase</u>
at $\Delta T = 250F$	900F to 1000F	Factor of 2.5
	1000F to 1100F	Factor of 2.2
	1100F to 1200F	Factor of 2.1
at $\Delta T = 500F$	700F to 800F	Factor of 1.3
	800F to 900F	Factor of 1.3
	900F to 1000F	Factor of 1.2
	1000F to 1100F	Factor of 1.2
	1100F to 1200F	Factor of 1.2

- (3) A downstream effect was also evident in the cold leg. At 50 hydraulic diameters downstream in the C3 holder, the rate of weight gain was 85% of what it was at zero downstream, while at 130 diameters, it was 66%.
- (4) As in the hot leg, the effect of oxygen was strongly significant. A change in the oxygen level from 12 to 50 ppm results in a corrosion rate increase by a factor of 3.8.
- (5) The temperature drop within a loop was a significant variable in that the effect of temperature depended on this variable. See (2) above. Maximum loop temperature was not a significant variable.
- (6) Using the same notation as in the hot leg, the following estimates of the residual variances obtain:

$$\begin{aligned}
 \sigma_s^2 &= 0.070 \\
 \sigma_w^2 &= 0.230 \\
 \sigma_b^2 &= 0.498 \\
 \text{Total Variance} &= 0.798 \\
 \text{Total Standard Deviation} &= 0.89
 \end{aligned}$$

95 percent Limits: Factor of 5.9

As in the hot leg, there is some inhomogeneity in the variances, although this is not as severe as in the hot leg. The average factor of ± 5.9 becomes ± 6.9 for corrosion rates less than about $7 \text{ mg/dm}^2\text{-mo}$, and about ± 4.7 for rates in excess of about $50 \text{ mg/dm}^2\text{-mo}$.

FIGURE 4 COLD LEG WEIGHT GAIN VERSUS TIME

- (7) In the cold leg, two prediction equations are required because of the dependence of the temperature effect on the value for ΔT , the temperature drop in the loop. These equations, plotted in Figure (2) of the conclusion section, are as follows:

$$\text{at } \Delta T = 250\text{F}$$

$$\ln R_2 = 13.12 - \left[\frac{18,170}{(T + 460)} \right] - 0.0032 (L/D) + 0.94 \ln O_x + \left[\frac{0.42}{(t + 1)} \right]$$

$$\text{at } \Delta T = 500\text{F}$$

$$\ln R_2 = 3.63 - \left[\frac{4360}{(T + 460)} \right] - 0.0032 (L/D) + 0.94 \ln O_x + \left[\frac{0.92}{(t + 1)} \right]$$

where

$$R_2 = \text{rate of weight gain (mg/dm}^2\text{-mo) } T, (L/D), O_x, \text{ and } t \text{ are defined as in the hot leg.}$$

In using the hot and cold leg prediction equations, certain considerations should be kept in mind:

- (1) These equations give the corrosion rates from time zero to time t . Steady-state rates may be found by letting $t \rightarrow \infty$ in each case, which is equivalent to dropping out the terms involving t from the equations.
- (2) Although the uncertainties in the predicted average corrosion rates are not large, there was considerable variation between the corrosion rates for samples exposed under nominally the same sets of conditions. This is measured by the plus or minus factors of 5.4 and 5.9, for the hot and cold legs respectively, within which 95 percent of the identically exposed samples are expected to fall. Since the "upper tail" of the distribution of individual corrosion rates is of greater practical importance than the average corrosion rate, this wide variation takes on great importance. Indications are that this does not truly reflect the variation in actual corrosion rates that will be encountered under a given set of conditions, but is rather due to deviations from nominal conditions for the exposed samples. Any large changes in oxygen content, for example, during a run would tend to increase this variation. Such changes were known to have occurred.
- (3) An empirical model, such as developed here, seeks to describe the results within the region of experimentation. The model of itself does not explain the observed phenomena. The dangers of extrapolation with an empirical model are obvious. This is especially true for the "time" variable in this study, because this is the variable that must be extrapolated considerably beyond the experimental conditions for plant application. For practical purposes, the other independent variables are less sensitive to the form of the model because there is less need to extrapolate their effects.

IV. DERIVATION OF CORROSION RATE PREDICTION EQUATIONS

4.1 Method of Estimation

There were three steps in the analysis leading to the prediction equation for either the hot or cold leg. First, weight change data for samples removed at intervals prior to the normal run completion time of 2800 hours were used to estimate the time effect. Next the 2800-hour virgin coupon data, adjusted to give steady-state rates on the basis of the estimated time effect in Step 1, were used to estimate the effects of the within run, or secondary variables (velocity, temperature, and downstreamness in the hot leg, and temperature and downstreamness in the cold leg.) All positions normally had 2800-hour data, except for H3, in which case average results for the other coupons were used on the basis of statistical tests, it was concluded that the within run effects were the same for all runs. Finally an evaluation of the effects of the between-run, or primary variables was made, using one value from each run, that value being the estimate of the "constant" parameter in Step 2.

Once the shorter time samples were used to evaluate the effect of the time variable as such, the analyses in Steps 2 and 3 made use of only the virgin 2800-hour sample data. There were two reasons for this, both of which are associated with the desire to avoid introducing bias in the data at the rather small expense of losing some precision because of exclusion of some of the sample data. The loss in precision is really quite small, since the components of variation due to differences between replicate samples was a minor source of variation relative to other sources. The two reasons are:

- (1) The sample positions within a loop had different numbers of sample slots, ranging from one to three, and a correspondingly different pattern of sample data. For example, at one position, there were generally five samples with exposures of 700, 2100, 1400, 1400 and 2800 hours, while at another position, only the one 2800-hour data point existed. A bias in the evaluation of the time effect, used to calculate steady-state corrosion rates as input to Step 2 in the analysis would affect the data from the two sample holders differently. This would be a consistent error from run to run and would persist in biasing the estimates of the effects of the secondary variables. By using only the 2800-hour data in this second step, the bias is removed.
- (2) The virgin 2800-hour samples were all in a given loop during the same period of time. They were, as a result, subjected to as nearly alike an environment as possible, exclusive of designed differences, of course. Short-term difficulties in loop operation would more nearly affect all samples to a comparable degree.

The estimation method discussed in the previous paragraphs was that used in deriving the final prediction equations. In the course of the program, as the data were made available, somewhat different approaches to the problem were used. These were not basically different from an estimation viewpoint. All terms entered the model in the same fashion for the different estimating methods. The methods differed with respect to the data which were included in the estimation, and in the sequence of steps used to arrive at the separate estimates of the parameters. It is encouraging to note (and not really surprising) that all methods give essentially the same prediction equations. They differ primarily in the errors associated with the parameter estimates for reasons which are made clear as these alternate approaches are discussed further in Appendix 6-4.

4.2 Hot Leg Equation

4.2.1 Time Effect

A discussion of the model used to describe the time effect is contained in Section 5.1 of this report. For a given sample, this is written:

$$R_1 = u \exp [b/(t + 1)]$$

where

R_1 = the rate of weight loss per unit area ($\text{mg}/\text{dm}^2/\text{month}$)

u, b = parameters

t = the exposure time in months (or, more exactly, in 700 hour units of time)

The parameter u represents the steady-state corrosion rate for the sample in question since, as $t \rightarrow \infty$, $\exp [b/(t + 1)] \rightarrow 1$. The value assumed by u is affected by the conditions under which the sample was exposed, and u is the quantity treated as the dependent variable in Step 2 of the analysis.

In Step 1, we are interested in the estimate of the parameter b . This determines when steady-state is reached. (For the model chosen, steady-state is never reached, except asymptotically. But, for all practical purposes, there comes a point when the corrosion rate is essentially constant with time.)

In estimating b for each run, data were restricted to include only reasonably large weight changes to minimize the effects of weighing errors. For each data set, consisting of corrosion rates for the virgin 700 hour, 1400 hour, and 2800 hour samples, b was estimated, as was its sampling variance. Normally, data from sample positions H1 inlet and H3R inlet were used. (All data were carbon corrected in this and following analyses, as explained in Appendix 6.1). The sampling variance is important because this enables us to see if the different estimates of b are indicative of true differences, or are simply due to sampling variation.

Seventeen estimates of b were found, ranging from a low of 0.22 to a high of 4.64, the average value being 2.26. Based on the sampling variance, we conclude that all seventeen estimates of b are estimating the same quantity, and there are no differences in this parameter either between or within loop runs. The over-all estimate of b is 2.26 ± 0.66 at the 95 percent confidence level.

To understand the significance of this parameter value as it relates to steady-state conditions refer to Figure 3. This figure gives the weight loss as a function of time for a typical sample. Observe from this curve that near steady-state is achieved early in life, essentially by the time the first data point is taken at 700 hours.

4.2.2 Effects of Secondary Variables

The within run variables were sample temperature, sodium velocity, and downstreamness. Further discussion of these variables is contained in Sections 5.2 through 5.4 of this report. As discussed in these sections, the model used to describe the effects of these secondary variables is

$$\ln u = b_0 + b_1 x_1 + b_2 x_2 + b_3 x_3$$

where

u = steady state corrosion rate ($\text{mg}/\text{dm}^2\text{-mo}$)

x_1 = natural logarithm of sodium velocity in fps

x_2 = reciprocal of absolute temperature in R or $\{[\frac{9}{F} + 460]^{-1}\}$

x_3 = downstream factor (dimensionless)

The steady-state corrosion rate was calculated for each virgin 2800-hour sample (or, in the event this sample was missing, as in the H3 position, average results for the samples were used). This steady-state rate was calculated using the average b value of 2.26 found in the previous section. With eight sample positions per loop, this resulted in eight data points per loop run.

For each run, estimates were found for b_1 , b_2 , and b_3 . It was important to test if these values differed from run to run. To test this, the residual variance was the statistic of interest. This is defined as the sum of the squared deviations between observed values and those predicted from some model, divided by the number of observations minus the number of parameters estimated in the model. Hence, it is a "goodness of fit" statistic. If the coefficient for temperature, for example, is truly the same for two loop runs, then the residual variance as calculated using an average value for the temperature coefficient for data from the two loop runs should not differ from that found by using the "best" estimate of the temperature coefficient in each run. There is a limit, of course, as to how small the residual variance can get, this being the variation observed between samples exposed under identical conditions. The aim is to find a model that will result in a residual variance no larger than this limiting value, but such a model is often difficult to develop because of the presence of some variables which affect the corrosion rate, but are not identified because they are not recognized as being variable quantities.

First, a test was made to see if the coefficients for velocity, temperature, and/or downstream differed significantly from loop to loop, or between run types (i.e., as a function of the primary variables). This was accomplished by estimating b_0 , b_1 , b_2 , and b_3 separately for each loop run, and by finding the residual variance under this model. This was found to be 0.231, based on 97 degrees of freedom. Estimates of b_1 ranged from 0.23 to 1.80; b_2 estimates varied between -9300 and -42,300; and the estimates of b_3 ranged from +0.05 to -1.25, showing the appreciable scatter from run to run.

Next, the model was written to permit a different estimate of the b_0 term for each loop run, but a common estimate for b_1 , b_2 , and b_3 . For this model, the residual variance was 0.366 with 179 degrees of freedom. This represents a significantly "poorer fit" than with the previous model, and suggests that there are some real differences in the effects of one or more of the secondary variables between loop runs. An investigation was undertaken to identify the source(s) of these differences.

This investigation showed that the effects of the secondary variables did not differ from loop to loop, nor were differences associated with different values of the primary variables of run maximum temperature, temperature drop, or oxygen level. Rather, the larger variance resulting from the over-all fit could not be traced to any identified variable, but was due to occasional "outlying" runs which, for some as yet unexplained reason, showed different effects for one or more of the three secondary variables. It should be emphasized that although the poorer fit occasioned by the use of common coefficients for the effects of velocity, temperature, and downstream is statistically significant, the residual variance is not appreciably larger than that resulting from fitting the loop runs separately.

There being greater appeal in using over-all estimates of the velocity, temperature, and oxygen effects in the absence of valid reasons why certain runs appear to differ, it was decided to use a model with the over-all estimates, and possibly focus attention on why certain runs are different at a later time.

The over-all estimates with 95 percent confidence limits are listed:

$$\begin{aligned} \text{(velocity) } b_1 &= 0.884 \pm 0.160 \\ \text{(temperature) } b_2 &= (-23.827 \pm 2.584) \times 10^3 \\ \text{(downstream) } b_3 &= -0.00676 \pm 0.00090 \end{aligned}$$

4.2.3 Effects of Primary Variables

The effects of the primary variables, and of loops, are examined by analyzing the b_0 estimates for each loop run, where these are based on the same values for the secondary variable coefficients. These estimates are listed below, classified by loops and by run types. See the introduction (Section I) for the material composition of the various test loops and the test conditions associated with the run types.

Estimates of b_0 Classified by Loop and Run Type

<u>Run Type</u>	<u>Loop 1</u>	<u>Loop 2</u>	<u>Loop 3</u>	<u>Loop 4</u>	<u>Loop 5</u>	<u>Loop 6</u>	<u>Average*</u>
I	17.67	-	16.28	17.29	18.07	17.17	17.30
II	16.09	16.10	16.41	16.99	15.61	14.73	15.97
III	15.40	-	16.33	16.18	15.68	-	15.56
IV	15.36	-	16.22	14.70	14.74	15.55	15.31
V	17.57	-	17.24	16.95	17.86	17.45	17.41
D	<u>17.49</u>	<u>-</u>	<u>-</u>	<u>-</u>	<u>-</u>	<u>-</u>	<u>-</u>
Average*	16.42		16.50	16.42	16.39	15.82	-

*Excluding Type D, and Loop 2, and inserting a "missing value" for Loop 6, Type III.

Again, in determining which effects are significant, we examined the value for the residual variance under alternate models. It is emphasized that this is now an analysis of b_0 values, and not of transformed corrosion rates per individual sample as in the previous section. Ideally, if there were no differences between loop runs other than those occasioned by one or more identified variables, we would obtain a residual variance of $(0.366)/8 = 0.046$, where the 0.366 value is the residual variance per sample, and 8 is the number of samples per b_0 value. Realistically, we do not hope to achieve a residual variance this small because of the difficulties associated with maintaining identical conditions from one loop run to the next. Any excess in our new residual variance over the 0.046 value is a measure of this "between-run" variability.

By observing the above table of b_0 values, it is apparent that the "strong" effect is that associated with the high oxygen run Types I and V. Analysis of several alternate models shows, in fact, that oxygen level is the only significant variable, there being no discernible differences between loops, nor due to the other primary variables of maximum run temperature, or temperature difference. To clarify a possibly bothersome point, there is naturally more corrosion in the 1200F maximum temperature runs than in the 1100F runs, simply because all the samples are at higher temperature. But, the greater amount of corrosion is consistent with that explained by the local temperature as a secondary variable, and hence, maximum run temperature as such is not a significant variable.

There is a possibility that ΔT , the temperature drop in a run, has some effect. This effect is not statistically significant and, if real, it is quite small (an estimated factor of 1.35 difference between the 250F ΔT and 500F ΔT runs).

Thus, there is no experimental evidence to include any primary variable but oxygen level in the model. Expressing $b_0 = b_0' + b_4 \ln \text{Ox}$ where Ox is the oxygen level in ppm, b_4 is estimated to be 1.156 ± 0.364 at the 95 percent confidence level. The observed residual variance between loop runs is 0.391 with this model, so that the following estimates of the two components of variance are found:

Within a run: Variance	=	0.366
Between runs: Variance	=	0.345 (i. e., $0.391 - 0.046$)
Total variance	=	0.711

4.2.4 Over-all Hot Leg Prediction Equation

Combining the results of the previous three sections, we obtain the over-all prediction equation for the corrosion rate in the hot leg.

$$\ln R_1 = 12.845 + 0.884 \ln V - \frac{23.827 \times 10^3}{(T + 460)} - 0.00676 (L/D) + 1.156 \ln \text{Ox} + \frac{2.26}{t + 1}$$

or

$$R_1 = V^{0.884} \text{Ox}^{1.156} \exp \left(12.845 - \left[\frac{23.827}{(T + 460)} \right] - 0.00676 (L/D) + \left[\frac{2.26}{(t + 1)} \right] \right)$$

where

R_1 = rate of weight loss (mg/dm²-mo)

V = sodium velocity (fps)

Ox = oxygen content (ppm)

T = sample of temperature (°F)

(L/D) = downstream factor (number of diameters downstream in isothermal region.)

t = months exposure

The steady-state result, with $t \rightarrow \infty$, was presented graphically in Figure 1 of Section II. The effect of the exposure term, $\frac{2.26}{t+1}$, is shown in Figure 3 of Section III.

The uncertainty of an average predicted value is small, the standard deviation being about 20 percent within the region of experimentation. However, the residual variance of an individual sample is large. For a sample selected at random from some position within a given loop run, the variance is 0.711, giving a standard deviation of 0.84. Therefore, with 95 percent confidence, we can expect its corrosion rate to be within a factor of 5.4 of the predicted rate. About one-half of this over-all variance comes as a result of differences between loop runs, with the remaining variation occurring within a run.

Two plots were made of the residuals (differences between observed and predicted logarithms of the corrosion rates) to detect lack of homogeneity in the variance, and to illustrate the meaning of the rather large "between run" variance. Figure 5 is a plot of residuals versus the logarithm of the predicted corrosion rate. There is some evidence here that the variation is greater at the low corrosion rates. This becomes more evident when the data are grouped in Table 4 with the frequency distributions of the residuals shown for four levels of corrosion rates. As summarized at the bottom of this table, the 95 percent confidence factor of ± 5.4 for all the data is ± 8.1 for the small corrosion rates, and about ± 4 for the larger rates, which are the ones of greatest practical interest.

TABLE 4
FREQUENCY DISTRIBUTION OF THE HOT LEG RESIDUALS

Observed-Predicted ln C. R.	PREDICTED ln C. R.				Over-all
	≤ 1	1-2	2-3	≥ 3	
>1.5	1	2	-	-	3
1.0-1.5	5	6	2	1	14
0.5-1.0	10	12	10	11	43
0-0.5	3	19	14	20	56
-0.5-0	9	17	13	15	54
-1.0-(-0.5)	7	5	4	5	21
-1.5-(-1.0)	4	1	2	3	10
<-1.5	3	1	2	1	7
$\sigma =$	1.046	0.722	0.706	0.675	0.843
$\pm 95\% \text{ C. L.} =$	± 8.1	± 4.2	± 4.1	± 3.9	± 5.4

The large between run variance is illustrated in Figure 6. Some runs have corrosion rates appreciably larger than that predicted by the model, notably Runs 3-7, 3-9, 4-2 and 4-7. Others are on the low side, e.g., 3-1, 4-5 and 5-4. Note that these run differences are not associated with given loops.

FIGURE 5 HOT LEG RESIDUALS

FIGURE 6 BETWEEN RUN HOT LEG VARIANCE

4.3 Cold Leg Equation

4.3.1 Time Effect

The same estimation procedure was used in the cold leg as was used in the hot leg. Individual estimates of the b parameter varied between -4.40 and 6.06, the average value being 0.92. This is appreciably more scatter than was observed in the hot leg. The scatter appeared to be caused by random effects, unassociated with any of the identified variables. Therefore, it is appropriate to use the average value of 0.92 for all cases, recognizing that there may be some real but unexplained differences in this time effect for some of the cases. The over-all estimate of $b = 0.92 \pm 0.82$ at the 95 percent confidence level gives rise to a typical weight gain versus exposure time curve as depicted in Figure 4, Section III.

4.3.2 Effects of Secondary Variables

In the cold leg, the within run variables were sample temperature and downstreamness, velocity being held constant at around 6 fps. The form of the mathematical model is the same as that used in the hot leg, and it may be written:

$$\ln w = a_0 + a_2 x_2 + a_3 x_3, \text{ where } w = \text{steady-state corrosion rate (weight gained) (mg/dm}^2\text{-mo)}$$

x_2, x_3 defined as in the hot leg.

The steady-state corrosion rate was calculated for each virgin 2800-hour sample, using an average b value of 0.92 found in the previous section. With four sample positions per loop, this resulted in four data points per loop run.

For each run, estimates of a_2 and a_3 were found. The residual variance found by fitting each loop run individually in this fashion was 0.143. In fitting an over-all model with different constants for each run, but with the same temperature and downstream coefficients, a residual variance of 0.444 resulted, appreciably larger than the 0.143 figure. This suggested quite strongly that the effects of temperature and/or downstream were somehow run-dependent.

The nature of this dependence is shown in the following table. The coefficients for the temperature effect, as estimated for each run, are given as a function of loop and run type.

TABLE 5
COLD LEG TEMPERATURE COEFFICIENTS
Temperature Coefficients ($\times 10^{-3}$)

<u>Run Type*</u>	<u>Loop 1</u>	<u>Loop 3</u>	<u>Loop 4</u>	<u>Loop 5</u>	<u>Loop 6</u>	<u>Average**</u>
I	- 1.6	- 4.1	- 9.4	- 1.9	- 5.6	- 4.5
II		- 9.6	- 7.1	3.7	6.1	- 1.5
III	- 8.0	- 7.4	-12.6			- 7.5
IV	-21.9	-14.1	-33.5		-15.5	-20.1
V	<u>-14.0</u>	<u>-10.3</u>		<u>-10.8</u>	<u>-24.9</u>	<u>-16.8</u>
Average**	- 9.2	- 9.1	-17.3	- 5.5	- 9.3	-10.1

* Defined in the introduction

** Adjusted for missing values.

Run Types I, II, and III are the 500F ΔT type runs, while for the other two types, ΔT was 250F. It is evident from the table listed on the previous page that the temperature effect is a function of run type, it being larger (in absolute value) for the 250F ΔT runs. If the data are separated into two groups, depending on the ΔT value, and the model fit separately to each group, the residual variance drops to 0.300, quite a reduction from the 0.444 value, but still higher than the 0.143 value found by fitting each run individually. However, there were no identified variables which, upon inclusion in the model, would reduce the variance below 0.300. Therefore, the problem reduced to fitting two models, one for the $\Delta T = 250F$ runs and one for the $\Delta T = 500F$ runs. The downstream effect was found to be the same for both groups, although individual estimates of this coefficient ranged from -1.72 to +0.93. Thus, we may write the over-all estimates of the within run or secondary variable effects as follows, where 95 percent confidence limits are shown.

$$\begin{aligned} \text{(Temperature)} \quad \hat{a}_2 &= (-4.36 \pm 2.00) \times 10^3 \text{ at } \Delta T = 500F \\ &= (-18.17 \pm 5.20) \times 10^3 \text{ at } \Delta T = 250F \\ \text{(Downstream)} \quad \hat{a}_3 &= (-0.0032 \pm 0.0040) \end{aligned}$$

The downstream effect is much less precisely determined in the cold leg than in the hot leg and, in fact, is not even significantly different from zero. In view of the strong significance of this effect in the hot leg, it is retained in the cold leg model also.

4.3.3 Effects of Primary Variables

The effects of the primary variables, and of loops were examined by analyzing the a_0 estimates for each run, keeping the $\Delta T = 250F$ and $\Delta T = 500F$ data separate. As was the case in the hot leg, only the oxygen effect was significant in the cold leg (except for the dependence of the temperature effect on the value of ΔT , as discussed in the previous section). The effect of oxygen was estimated separately for each of the two ΔT groups, but was not found to differ significantly between groups. Therefore, an average oxygen effect was computed. Expressing $a_0 = a_0' + a_4 \ln \text{Ox}$ where Ox is the oxygen level in ppm, a_4 was estimated to be 0.94 ± 0.39 at the 95 percent confidence level. The observed residual variance between loop runs is 0.573 with this model, so that the following estimates of the two components of variance are found:

$$\begin{aligned} \text{Within a run:} \quad \text{Variance} &= 0.300 \\ \text{Between runs:} \quad \text{Variance} &= 0.498 \quad \text{i.e., } 0.573 - 0.300/4 \\ \text{Total Variance} &= 0.798 \end{aligned}$$

Note that this agrees quite well with the hot leg results. Again, the variance between runs is very large.

4.3.4 Over-all Cold Leg Prediction Equation

Combining the results of the previous three sections, we obtain the over-all prediction equation for the corrosion rate in the cold leg.

At $\Delta T = 250F$:

$$\ln R_2 = 13.12 - 18.17 \times 10^3 / (T + 460) - 0.0032 (L/D) + 0.94 \ln O_x + 0.92 / (t + 1)$$

or:

$$R_2 = O_x^{0.94} \exp \left[13.12 - 18.17 \times 10^3 / (T + 460) - 0.0032 (L/D) + 0.92 / (t + 1) \right]$$

and at $\Delta T = 500F$:

$$\ln R_2 = 3.63 - 4.36 \times 10^3 / (T + 460) - 0.0032 (L/D) + 0.94 \ln O_x + 0.92 / (t + 1)$$

or:

$$R_2 = O_x^{0.94} \exp \left[3.63 - 4.36 \times 10^3 / (T + 460) - 0.0032 (L/D) + 0.92 / (t + 1) \right]$$

where:

R_2 = rate of weight gain to time t. (mg/dm²-mo)

O_x = oxygen content (ppm)

T = sample temperature (°F)

(L/D) = downstream factor

t = months exposure

We can, if we choose, express this as one equation by writing the coefficient for the temperature term as a function of ΔT . However, little is gained by doing this, and it is perhaps wiser to present the results as two separate equations to discourage interpolation to other values of ΔT .

The prediction equations are also presented graphically in Figure 2 of Section II (Velocity is fixed in the cold leg at about 6 fps). This curve suggests the nature of the dependence of the temperature effect on ΔT . For a loop maximum temperature of 1200F, the sample temperatures in the cold leg are as follows:

<u>Position</u>	<u>$\Delta T = 250F$</u>	<u>$\Delta T = 500F$</u>
C1	1100	1100
C2	1000	1000
C3 Outlet	950	700
C3 Outlet	950	700

At positions C1 and C2, the curves in Figure 2 show that the corrosion rates are about the same. At the C3 position, for the $\Delta T = 250F$ curve, we expect a corrosion rate of about 50 mg/dm²-mo. For the $\Delta T = 500F$ curve, we expect a rate of about 35 mg/dm²-mo, certainly not different from the 50 mg/dm²-mo figure. The same comparison holds for a 1100F maximum temperature loop. Thus, it appears that the

rate of weight gain in the cold leg is a function of sample position, rather than sample temperature; the physical distance downstream from the beginning of the cold leg is the significant variable. This being the case, we should use caution in interpreting the significance of the temperature effect in the cold leg.

The uncertainty of an average predicted value in the cold leg is about 40 percent at one standard deviation. As in the hot leg, this is a small uncertainty compared with the residual variance of our individual sample. This latter variance is estimated to be 0.798 for a sample selected at random from some position within some loop. The standard deviation is 0.89 which means that with 95 percent confidence, the observed corrosion rate of a sample will be within a factor of 5.9 of the predicted rate.

Plots were made of the residuals in the cold leg. Figure 7 is a plot of residuals versus the predicted logarithm of the corrosion rate. Some dependence of scatter on corrosion rate is noted here also. This is better shown in Table 6, where the frequency distributions of residuals are given. As summarized at the bottom of this table, the average uncertainty factor of ± 5.9 for the cold leg is ± 6.9 for smaller corrosion rates ($< 7 \text{ mg/dm}^2\text{-mo}$), and ± 4.7 for the larger rates of interest ($> 50 \text{ mg/dm}^2\text{-mo}$).

TABLE 5
FREQUENCY DISTRIBUTION OF THE COLD LEG RESIDUALS
PREDICTED $\ln \text{ C. R.}$

Observed-Predicted $\ln \text{ C. R.}$	1-2	2-3	3-4	≥ 4	Over-All
1.5-2.0	1	3	2		6
1.0-1.5	2	4		2	8
0.5-1.0	2	7	4	3	16
0.0-0.5	2	8	6	3	19
-0.5-0.0	2	9	2	2	15
-1.0-(-0.5)	1	6	4	4	15
-1.5-(-1.0)	2	2	3	1	8
-2.0-(-1.5)		1			1
σ	0.968	0.866	0.868	0.772	0.89
$\pm 95\% \text{ C. L.}$	± 6.9	± 5.7	± 5.7	± 4.7	± 5.9

In Figure 8, the large between run variance is illustrated. Since there are only four positions per run in the cold leg, the average residuals per loop-run show more scatter than in the hot leg. In Figure 9 is shown a plot of the hot leg average run residual versus the corresponding cold leg residual. Note that, in general, those biased high in the hot leg were also biased high in the cold leg, as expected. However, this is not a well-defined relationship.

FIGURE 7 RESIDUALS VERSUS PREDICTED LOGARITHM OF CORROSION RATE

FIGURE 8 BETWEEN RUN VARIANCE

FIGURE 9 HOT LEG AVERAGE RUN RESIDUAL VERSUS CORRESPONDING COLD LEG RESIDUAL

V. FURTHER DISCUSSION OF EACH VARIABLE

A fully developed theory of corrosion rates of steel alloys in the anticipated operating conditions of sodium cooled reactors would have allowed all the controlling variables to be separated out in their correct dimensional forms and would have provided the correct forms of the corrosion-rate equations. The statistical problems would then be centered on providing maximum precision in estimating the constants (parameters) in the corrosion rate equations. In actuality, however, the theory is not this complete, making it even more necessary and vital to obtain experimental data to cover this region of experimentation. This being the state-of-the-art, theoretical considerations provide clues, but not final answers as to which independent variables should be used and what forms they should take. The amount of distinction that can be made between different and sophisticated forms of the independent variables is always limited by the large random variation experienced in corrosion data no matter how perfect the experimental design may be.

In this section, a further discussion is given of each variable as it enters into the prediction equations.

5.1 Time

During the sodium mass transfer study, it was observed that after an initial period of exposure in which accelerated corrosion rates occurred steady-state is reached in which the corrosion rate is constant. The empirical model must describe this situation. A model of the form: $R = a \exp \left[b \left[f(t) + c \right]^{-1} \right]$ is properly descriptive. In this model R = the corrosion rate at time t (per unit area per unit time) a, b, c are parameters of the model $f(t)$ is a function of t such that $f(0) = 0$, and such that $f(t) \rightarrow \infty$ as $t \rightarrow \infty$.

As $t \rightarrow \infty$, it is seen that $R \rightarrow a$, so a represents the steady-state corrosion rate. When $\ln R$ is plotted against $Z = \left[f(t) + c \right]^{-1}$ we get a straight line with intercept $\ln a$ and slope b . In fitting this model $f(t)$ and c were first chosen. The simplest choice for $f(t)$ is $f(t) = t$, and this has been used to date. It has since been suggested that $f(t) = \sqrt{t}$ may be more attractive from a theoretical point of view but on the basis of the data to date, there is little reason for selecting one form of $f(t)$ over the other. The parameter c was selected by plotting several sets of data and selecting that value which most nearly linearized the data. With t expressed in 700-hour units, a value of c near one was found to accomplish this. The final empirical model chosen was therefore:

$$R = a \exp \left[b(t + 1)^{-1} \right].$$

It is emphasized that this is an empirical model, and therefore suffers from the deficiencies associated with such models, notably, the danger of extrapolation. This is an important consideration in corrosion work where an ultimate aim is the prediction of long-term corrosion rates.

5.2 Velocity

Within the region of experimentation, the corrosion rates increased with increasing velocities in a predictable and highly significant manner. In order to understand the mechanism of corrosion controlling this effect, however, it is necessary to determine whether this is really a velocity effect or a mass flow effect. For the particular geometries in the sample holders in this test the velocity and mass flow are directly proportional so that what is called a velocity effect could just as well be called a mass flow effect.

5.3 Temperature

Temperatures enter into the analysis in several forms, $T_{\max}$, ΔT , and local temperature T . The influence of temperature on the corrosion rate of an individual sample is most certainly characterized by some function of local temperature. The primary variables $T_{\max}$, and ΔT , are essentially design artifices used to create the experimental conditions needed for a comprehensive test. As further illustration of this, the regression coefficient of the ΔT term when it has been included in the statistical model has not been significant. Further, increases in the corrosion rates in the runs with higher $T_{\max}$ values have been shown to be consistent with those rates predicted by the local temperature effect. The Arrhenius form of the temperature factor, suggested from the theory of chemical reaction rates, uses the reciprocal of the absolute temperature as the independent variable when the natural logarithm of the corrosion rate is the dependent variable. The estimated regression coefficient of this variable, then, has a physical interpretation as the activation energy necessary to initiate the corrosion process.

5.4 Downstream

It has been apparent from the first runs that samples placed downstream in an isothermal region experienced lower corrosion rates. This was consistent with a theory that relates the corrosion rate of a sample to the degree of unsaturation or to the amount of oxygen available. The aspect of this effect that was unexpected was that the effect was so strong and readily discernible with weight change data. A considerable number of sophisticated models, using different forms of the downstream factor, have been tried in order to describe this effect. Considering the large amount of variation experienced in corrosion data, however, it is not surprising that no particular form was significantly best. The number of diameters downstream has been used because it is simple and unconfounded with other variables, it agrees with experimental results, and is consistent with the theory that the corrosion rate should be proportional to the degree of unsaturation.

5.5 Oxygen

If a model of the form $y = a + bz$ is fitted to data by a least squares technique, where the z values are observed at only two levels z_1 and z_2 , the prediction equation will then pass through the y averages $\bar{y}_1$ and $\bar{y}_2$. In this sense then the form of the z 's (e.g., $z = x^2$, $z = x^4$ etc) is irrelevant to the determination of whether the fitted line is significant. The primary variable, the oxygen level, is tested at only two levels (12 ppm and 50 ppm) so that it is not possible to test the form in which the independent variable should enter into the corrosion rate equation. The difference between the two levels has been shown to be highly significant, but the experimental data reveal nothing about the correct form of the variable.

VI. APPENDIX

6.1 Carbon Correction

In certain of the loop runs, the rather significant amount of carbon movement that occurred made it necessary to correct the weight change data to reflect true metal loss. This correction was accomplished by analyzing selected samples from each loop run for carbon content after the 2800-hour exposure. These values expressed as weight percentages, were then used to estimate the carbon content of all samples in the run. Knowing the sample weights, the weight of the carbon could be obtained. This was then applied to the total weight change of each sample coupon to result in a weight change unaffected by the carbon transfer.

Unfortunately, from a weight change analysis viewpoint, the amount of carbon transfer in some of the runs was appreciable, compared with the amount of corrosion observed. This fact contributes to the rather large amount of variation observed in the corrosion data, and can also be a source of bias.

6.2 Data Transformation for Data Having the "Wrong" Sign

In the hot leg, the statistic of interest is the observed rate of weight lost per unit time, while in the cold leg, it is the rate of weight gained per unit time. Restricting attention to the hot leg (the extension to the cold leg is obvious), we write:

$$R = w/At$$

where:

R = corrosion rate in $\text{mg}/\text{dm}^2\text{-mo}$

w = observed weight loss in mg

A = area of sample coupon in dm^2

t = exposure time in months.

A and t are considered to be determined without error, but w is affected by weighing errors. (This includes all variations introduced in the weighing process, such as cleaning the sample.)

Because the variation between observed corrosion rates increases with increased rates, a logarithmic transformation is used to stabilize the variance, and the statistic of interest is $\ln R$. Now, when weight losses are very small, some weight changes may be recorded as being weight gains rather than weight losses because of variation introduced by the weighing process. This makes the observed w , and hence y , a negative quantity, and poses a problem since logarithms of negative numbers are meaningless.

One course of action could be to disregard all such negative values, but this creates a bias since the existence of a negative number is a meaningful bit of information; it is evidence that the true weight loss for the sample was very small. Another solution would be to add a small amount to all observed values. This, in effect, asserts that a bias is introduced in the weighing process, which is not really the case. Further, it creates the problem of how much to add to each result.

A better solution to the problem is to use the data transformation required, by the assumed model, to stabilize the variance. We proceed as follows. The observed w may be written as a "true" value (w_0), representing the long-term average for identical samples exposed under identical conditions, plus a deviation (ϵ), representing random variation exclusive of measurement error, plus a component due to error (η) introduced in the weighing process.

$$w = w_0 - \epsilon - \eta.$$

We know that the variance of ϵ increases as w increases with the standard deviation being proportional to the mean. The dependence is expressed as follows:

$$\sigma_{\epsilon}^2 = k^2 w^2.$$

The weighing error is assumed to be constant, independent of w . Its variance is denoted by σ_{η}^2 . Thus, the observed variance in w is:

$$\sigma_w^2 = k^2 w^2 + \sigma_{\eta}^2.$$

We wish to stabilize the variance, that is, express the statistic as a function of w such that the variance of this function is independent of w .

Denote the function of w we wish to find as $\phi(w)$. We may write, approximately:

$$\sigma_{\phi(w)}^2 \approx \left(\frac{\partial \phi(w)}{\partial w} \right)_{w_0}^2 \sigma_w^2$$

where the partial derivative is evaluated at w_0 .

Since we desire $\sigma_{\phi(w)}^2$ to be constant, denote this by C , and solve for ϕ .

$$C = \left(\frac{\partial \phi(w)}{\partial w} \right)_{w_0}^2 \sigma_w^2$$

$$\frac{\sqrt{C}}{\sigma_w} = \left(\frac{\partial \phi(w)}{\partial w} \right)_{w_0}$$

from which:

$$\begin{aligned} \phi(w) &= \sqrt{C} \int \frac{1}{\sigma_w} dw \\ &= \sqrt{C} \int \frac{1}{\sqrt{k^2 w^2 + \sigma_{\eta}^2}} dw \\ &= \frac{\sqrt{C}}{k} \ln \left(kw + \sqrt{k^2 w^2 + \sigma_{\eta}^2} \right) \end{aligned}$$

It is the form of the transformation that is of particular interest. The coefficient $\sqrt{C/k}$ may be ignored since it is a constant, and the variance of $\phi(w)$ will be stabilized (i.e., become independent of w) whether or not this is included as part of the transformation.

The specific transformation used in these analyses is:

$$w' = \ln \left\{ \frac{w + \sqrt{w^2 + 0.5}}{2} \right\}$$

Note that as w gets large, w' approaches $\ln w$, the simple logarithmic transformation. For the great majority of the sample points, w' and $\ln w$ are essentially identical, and the entire presentation of the prediction equations assumes the use of the simple logarithmic transformation. In the specific transformation used, the 2 in the denominator is chosen solely to make $w' \rightarrow \ln w$. Clearly, any constant would stabilize the variance. The 0.5 under the radical sign is an estimate of σ_{η}^2/k^2 .

6.3 The Fractional Replicate Plan

The effects of the between run, or primary, variables were evaluated by changing loop conditions between runs. The variables identified and controlled in a given loop were as follows:

ΔT = Sodium temperature differential in the loop (F)

$T_{\max}$ = Maximum sodium temperature in the loop (F)

Ox = Sodium oxide level (ppm)

Two levels of each variable were under investigation:

ΔT = 250F; 500F

$T_{\max}$ = 1100F; 1200F

Ox = 12 ppm; 50 ppm

A complete factorial experiment would have required that each loop have eight runs corresponding to the eight possible combinations of the levels of ΔT , $T_{\max}$, and Ox. The resulting eight "degrees of freedom" would be used to estimate the following effects:

<u>Effect</u>	<u>Degrees of Freedom</u>
Mean	1
ΔT , $T_{\max}$, Ox	3
Two-factor interactions	3
Three-factor interactions	$\frac{1}{8}$

Eight runs per loop would have required too extensive a program. Since the main effects (ΔT , $T_{\max}$, Ox) were thought to dominate in the sense that any interactions, if they existed, would be small, it was decided that the complete factorial experiment did not have to be run, but rather, that some fraction of this would suffice.

Estimates of the main effects could be found with a one-half replicate, as follows:

<u>Oxygen (ppm)</u>	<u>$T_{\max}$ (F)</u>	<u>ΔT (F)</u>
50	1200	500
12	1100	500
12	1200	250
50	1100	250

With five loops operating under these conditions, the 20 degrees of freedom would be used as follows:

<u>Effect</u>	<u>Degrees of Freedom</u>
mean	1
ΔT , $T_{\max}$, Ox	3
loops	4
Interaction: loops with primary variables	<u>12</u>
	20

It being assumed that the effects of ΔT , $T_{\max}$, and Ox are not loop dependent, this leaves 12 degrees of freedom to estimate the residual variance between runs.

A fifth run (run type II) was made in each loop at the following set of conditions:

Oxygen = 12 ppm

$T_{\max}$ = 1200F

ΔT = 500F

This resulted in 5 more runs, with 4 additional degrees of freedom to estimate the between-runs residual variance, and 1 to determine the significance of some interaction between the three primary variables, although the identity of such an interaction, if significant, would remain unknown.

It is of interest to measure the information resulting from the five-run fractional replicate, compare this with the information that would have resulted had the one-half replicate been used, and, finally, determine the effect of running additional runs either within the confines of the original design, or exterior to it. This information will be measured by determining the standard deviation associated with the estimate of each effect. Loop differences having been shown to be non-significant, we combined data from all loops in this treatment.

For simplicity, call the levels of the primary variables -1 and +1. This corresponds to making the following transformations on the variables:

$$v_1 = \frac{\ln \text{Ox} - 3.19}{0.71}$$

$$v_2 = -\frac{(T'_{\max} - 0.621)}{0.020}, \text{ where } T'_{\max} = \frac{10^3}{(T_{\max} + 460)}$$

$$v_3 = \frac{\ln \Delta T - 5.86}{0.34}$$

The model is written:

$$\begin{aligned} f(v_1, v_2, v_3) &= C_0 + C_1 v_1 + C_2 v_2 + C_3 v_3 \\ &= C_0' + C_1' \ln \text{Ox} + C_2' T'_{\max} + C_3' \ln \Delta T \end{aligned}$$

where the standard deviations of $\hat{C}_1'$, $\hat{C}_2'$, and $\hat{C}_3'$ are required.

Since $C_1' = C_1/0.71$, $C_2' = -C_2/0.020$, and $C_3' = C_3/0.34$, we have the following relationships between the variances of the C_i' estimates and the C_i estimates.

$$\text{var } \hat{C}_1' = 1.98 \text{ var } \hat{C}_1$$

$$\text{var } \hat{C}_2' = 2500 \text{ var } \hat{C}_2$$

$$\text{var } \hat{C}_3' = 8.65 \text{ var } \hat{C}_3$$

We proceed to find these variances. The data for the five-run replicate appear as follows:

$\underline{v_1}$	$\underline{v_2}$	$\underline{v_3}$	<u>Number of Observations</u>
1	1	1	5
-1	-1	1	5
-1	1	-1	5
1	-1	-1	5
-1	1	1	5

The variances of each estimate are found from the diagonal elements of the inverse of the following symmetric matrix:

$$S = \begin{pmatrix} n & \Sigma v_1 & \Sigma v_2 & \Sigma v_3 \\ \Sigma v_1^2 & \Sigma v_1 v_2 & \Sigma v_1 v_3 \\ & \Sigma v_2^2 & \Sigma v_2 v_3 \\ & & \Sigma v_3^2 \end{pmatrix}$$

For the above data, this matrix becomes:

$$S = \begin{pmatrix} 25 & -5 & 5 & 5 \\ & 25 & -5 & -5 \\ & & 25 & 5 \\ & & & 25 \end{pmatrix}$$

which has inverse:

$$S^{-1} = 1/160 \begin{pmatrix} 7 & 1 & -1 & -1 \\ & 7 & 1 & 1 \\ & & 7 & -1 \\ & & & 7 \end{pmatrix}$$

The variance of each of the $\hat{C}_i$ is therefore $(7/160)\sigma_T^2$, where σ_T^2 is the variance between run averages. This was estimated to be 0.391 for the hot leg, so the variances of the coefficients for the primary variable effects are as follows:

$$\text{Oxygen: } \text{var } \hat{C}_1' = (1.98) (7/160) (0.391) = 0.0339 = \sigma_{\hat{C}_1'}^2 = 0.184$$

$$T_{\text{max}}: \text{var } \hat{C}_2' = (2500) (7/160) (0.391) = 42.8 = \sigma_{\hat{C}_2'}^2 = 6.54$$

$$T: \text{var } \hat{C}_3' = (8.65) (7/160) (0.391) = 0.148 = \sigma_{\hat{C}_3'}^2 = 0.385$$

From the size of these precisions, it is clear that effects must be quite large before being detectable.

Changing the experimental design by inclusion or exclusion of certain runs affects only the inverse matrix S^{-1} . The between-run variance is unaffected.

A measure of the inter-dependence between estimates of the affects is found by examining the off-diagonal elements of the S^{-1} matrix. Specifically, the correlation coefficient between any two parameter coefficients C_i , C_j is given by the relationship:

$$\rho_{ij} = \frac{S_{ij}^{-1}}{\sqrt{S_{ii}^{-1} \cdot S_{jj}^{-1}}}$$

where:

$$S_{ij}^{-1} = i, j \text{ element of the } S^{-1} \text{ matrix}$$

For the 5-run fractional replicate, we have for all i, j :

$$|\rho_{ij}| = \frac{1}{\sqrt{(7)(7)}} = 0.14$$

which is quite small, and no cause for concern; the effects are pretty much independent of one another.

Suppose we had run only the one-half replicate. Then, the S matrix becomes:

$$S = \begin{bmatrix} 20 & 0 & 0 & 0 \\ & 20 & 0 & 0 \\ & & 20 & 0 \\ & & & 20 \end{bmatrix}$$

and

$$S^{-1} = 1/20 \begin{bmatrix} 1 & 0 & 0 & 0 \\ & 1 & 0 & 0 \\ & & 1 & 0 \\ & & & 1 \end{bmatrix}$$

In this case, all effects are completely uncorrelated. The variance of each coefficient is $(1/20)\sigma_T^2$, which yields the following variance for the $\hat{C}_i'$:

$$\text{Oxygen: } \text{var } \hat{C}_1' = (1.98)(0.05)(0.391) = 0.0387 = > \sigma_{\hat{C}_1'} = 0.197$$

$$T_{\max}: \text{var } \hat{C}_2' = (2500)(0.05)(0.391) = 48.9 = > \sigma_{\hat{C}_2'} = 6.99$$

$$\Delta T: \text{var } \hat{C}_3' = (8.65)(0.05)(0.391) = 0.169 = \sigma_{\hat{C}_3'} = 0.411$$

Comparing these σ 's with those resulting from the 5-run replicate, we see that little improvement in precision was effected by running the additional run, although it did provide data to test for the significance of any interaction.

If the complete 8-run factorial experiment were run, then:

$$S^{-1} = 1/40 \begin{bmatrix} 1 & 0 & 0 & 0 \\ & 1 & 0 & 0 \\ & & 1 & 0 \\ & & & 1 \end{bmatrix}$$

and, clearly, the effect is to reduce all the standard deviations by a factor of 2 over the half-replicate.

The importance of the between-run residual variance of 0.391 should be stressed. This is really the sum of two components, the component coming from the variability within a run, and that coming from differences between runs. Specifically, in the hot leg,

$$0.391 = 0.345 + 0.366/8$$

this latter component being the within run variance divided by the number of sample coupons per run. Note the important consideration that even if the number of sample coupons per run were made infinitely large, the observed variance between runs would not get smaller than 0.345, and the standard deviation of 0.184 observed for the oxygen effect would only be decreased to 0.172, a negligible improvement.

Clearly, as far as the evaluation of the primary variables is concerned, the number of sample coupons used per run was ample, and the exclusive use of the data from the virgin 2800-hour samples was justified.

We consider finally the evaluation of the within-run or secondary variable. For a typical run, the hot leg data appear as follows:

<u>(Velocity)</u>	<u>(Temperature)</u>	<u>(Downstream)</u>
-1	-1	-2
1	-1	-1
-1	0	-2
1	0	-1
1	1	-2
1	1	-1
-1	1	1
1	1	2

where

$$N_4 = \frac{\ln \text{vel.} - 2.34}{0.55} \text{ (for a 6 fps-18 fps loop run)}$$

$$N_5 = - \frac{(T' - 0.643)}{0.042}, \text{ where } T' = \frac{10^3}{(T + 460)} \text{ and for a } 1200\text{F } T_{\text{max}}^{\text{run}}$$

$$v_6 = \frac{[(L/D) - 2.03]}{0.75}$$

For any one run, the S^{-1} matrix is shown to be as follows:

$$\begin{bmatrix} 0.2193 & 0.0288 & 0.1042 & 0.0814 \\ & 0.1411 & 0.0358 & 0.0033 \\ & & 0.2476 & 0.0684 \\ & & & 0.0847 \end{bmatrix}$$

As a first comment, the off-diagonal elements are used to find the correlation coefficients between the various parameter estimates:

$$\text{velocity - temperature: } \rho = \frac{-0.0358}{\sqrt{(0.1411)(0.2476)}} = -0.19$$

$$\text{velocity - downstream: } \rho = \frac{0.0033}{\sqrt{(0.1411)(0.0847)}} = -0.03$$

$$\text{Temperature - downstream: } \rho = \frac{0.0684}{\sqrt{(0.2476)(0.0847)}} = -0.47$$

The effects are not badly correlated, except that the correlation between the temperature and downstream effects is higher than desirable. Since the downstream was unanticipated, this degree of correlation is understandable.

For any one run, the within run variance is estimated to be 0.366. Using this result, plus the elements of the inverse matrix, and the transformations, we arrive at the following precision estimate for each effect:

velocity: variance $\hat{C}_4' = (3.31) (0.1411) (0.366) = 0.171 = > \sigma \hat{C}_4' = 0.414$

temperature: variance $\hat{C}_5' = (567) (0.2476) (0.366) = 51.4 = > \sigma \hat{C}_5' = 7.17$

downstream: variance $\hat{C}_6' = (1.78) (0.0847) (0.366) = 0.0552 = > \sigma \hat{C}_6' = 0.235$

For the 25 runs from the 5-run factorial replicate, these standard deviations are divided by $\sqrt{25}$ or 5.

The within run variance of 0.366 is made up of two components; one relating to the variance between sample positions, and one to the variance between sample coupons at a given position. This latter quantity was estimated directly, the estimate being 0.076. Therefore, since only one coupon was used per position in the analysis, the between-position variance is estimated to be $0.366 - 0.076 = 0.290$. This is additional evidence to show that the use of only the data from the virgin 2800-hour coupons scarcely affects the precisions of the estimates. For example, had we been able to use 3 coupons per sample position, the within-run variance would still be $0.290 + 0.076/3 = 0.315$, which is not a large reduction from the 0.366 value. Clearly, the variation between replicate samples exposed to the same environment is relatively small, and little is gained by including data from all samples in the analysis. The primary motivation behind the use of such replicate samples (from a weight change viewpoint) is that it permits an estimation of the "time" effect.

6.4 Alternate Estimating Methods

During the course of the program, as the data were being developed, various methods of estimation were used. Preliminary results were reported at various stages in the program, these results being based on data accumulated up to the time of each report. It was recognized throughout that the final method of analysis would await the complete set of data, using all the information available at that point of time to select this best approach to the problem. This step was taken, and the results of what is considered to be the best way to estimate the parameters formed the basis of the main body of this report.

Nevertheless, it is instructive to document these other approaches to the problem and to point out why they were not used in the final analysis. It should be recognized that all approaches would be expected to give about the same appraisal of the effects of the different variables; they differ mainly in how limits of uncertainty are attached. It is, nonetheless, comforting to note that the final estimated prediction model is relatively insensitive to which approach is used.

These approaches (excluding that which forms the basis of this report) are basically three in number. In the first two approaches, the effects of the within run variables were estimated separately for each run, just as in the method chosen, except that all data points were included. Then, the between run variables were investigated either by using as input data for each run an estimated steady state corrosion rate at some specified set of conditions, or by simply using as the statistic the total weight change in the hot leg. In the third approach, all the data were used simultaneously to fit one overall regression model which included as terms in the model all the within and between run variables.

The primary difficulty with these approaches was associated with the inability to obtain valid estimates of the uncertainties assigned to each parameter estimate. For the approach in which the run statistic was the predicted corrosion rate at some set of conditions, clearly the points did not have common variance. Although a weighted regression could have perhaps been used in obtaining the estimates of the between-run parameters, the weights to use would have depended strongly on which set of conditions was used as a base point in obtaining the between run estimates. Further, a series of different base points would logically have to be investigated to see how important this selection was on the estimates of the between run parameters.

A similar difficulty arises when trying to fit all the data simultaneously by one grand model that includes the within and between run variables. The overall scatter in the data, which is used to estimate the residual variance, which, in turn, is used to assign limits of uncertainty on the parameter estimates, is a mixture of the within-run and the between run variances. The size of this residual is sharply affected by the number of runs involved relative to the number of data points within each run. Clearly, in this instance, the residual variance is a rather meaningless quantity.

Of the alternate methods used, the one employing total weight lost in the hot leg as a test statistic is the most defensible. Here, however, more attention is directed at certain sample positions than at others due to the larger number of samples taken at these positions. This is not a strong criticism.

The possible objection to the method used in arriving at the final model(s) is that it "does not make use of all the data". This, of course, is not true since all the data are used in estimating the effect of time, for one thing. They were not used in subsequent steps of the analysis because of the wish to avoid introducing a bias in the data (This is discussed more fully in Section 4.1). It turns out, as shown in detail in Appendix 6.3, that very little information was lost in using only the eight sample points per run, simply because the "within run" variation is so large relative to the "within sample slot" variation, as is the "between run" variance relative to the "within run" variability. If such had not turned out to be the case, more of the sample coupons would have been utilized at the expense of introducing some bias into the estimates.

Although these alternate methods had shortcomings associated with the assignment of error limits to the parameter estimates, it is nevertheless comforting to note that estimates of the effects were pretty much the same no matter which estimating approach was used. This is illustrated in the following tables in which comparisons of the parameter estimates are given for the various approaches. The basic form of the model is the same in all cases.

<u>Within Run Estimates (hot leg)</u>			
<u>Effect</u>	<u>Method Reported ($\pm 95\%$)</u>	<u>Using All Samples</u>	<u>Overall Model</u>
Time	2.26 $\pm$ 0.66	1.96	1.46
Velocity	0.884 $\pm$ 0.160	1.01	0.82
Temperature	-23,827 $\pm$ 2,584	-26,690	-25,948
Downstream	-0.00676 $\pm$ 0.00090	-0.0063	-0.0059

<u>Between Run Estimates (hot leg)</u>				
	<u>Method Reported</u>	<u>Predicted* Corrosion Rates</u>	<u>Total Weight Losses</u>	<u>Overall Model</u>
Oxygen	1.156 $\pm$ 0.364	1.41	1.21	1.25
ΔT	0	0	0	0.65
T Max	0	0	0	0

*At a specified set of conditions

Within Run Estimates (Cold leg)

<u>Effect</u>	<u>Method Reported</u>	<u>Using All Samples</u>	<u>Overall Model</u>
Time	0.92 $\pm$ 0.82	0.40	Not Included
Temperature:	-18,170 $\pm$ 5200 at $\Delta T = 250$	-11,080	-11,770
	-4360 $\pm$ 2000 at $\Delta T = 500$	-2570	-4268
Downstream	-0.0032 $\pm$ 0.0040	-0.0040	-0.0064

Between Run Estimates (Cold leg)

<u>Effect</u>	<u>Method Reported</u>	<u>Overall Model</u>
Oxygen	0.94 $\pm$ 0.39	0.79
ΔT	0	0
T Max	0	0

LIST OF SODIUM MASS TRANSFER PROJECT REPORTS

1. Lockhart, R. W., Billuris, G., and Lane, M. R., "Sodium Mass Transfer: I Test Loop Design," GEAP-3725, June 1962.
2. Lockhart, R. W., et al, "Sodium Mass Transfer: II Screening Test Data and Analysis - Mass Transfer Results," GEAP-3726, Volume 1, May 1962.
3. Hetzler, F. J., and Young, R. S., "Sodium Mass Transfer: II Screening Test Data and Analysis - Metallurgy," GEAP-3726, Volume 2, June 1962.
4. Lockhart, R. W., "Sodium Mass Transfer: II Screening Test Data and Analysis 1961 Corrosion Sample Data," GEAP-3726, Volume 3, May 1962.
5. Alter, H. W., and McManus, P. A., "Sodium Mass Transfer: III The Application of Liquid Ammonia as a Leaching Agent," GEAP-4006, April, 1962.
6. Pohl, L. E., "Sodium Mass Transfer: IV 1962 Corrosion Sample Data," GEAP-4181, January, 1963.
7. Lockhart, R. W., "Sodium Mass Transfer: V 1962 Test Run Reports," GEAP-4182, June, 1963.
8. Dunn, E. L., "Sodium Mass Transfer: VI Statistical Correlation of 1961-1962 Corrosion Data," GEAP-4183, February, 1964.
9. Sabol, W. W., and Lockhart, R. W., "Sodium Mass Transfer: VII Methods for Determining Impurities in Sodium Samples," GEAP-4178, September, 1963.
10. Mottley, J. D., "Sodium Mass Transfer: VIII Corrosion of Stainless Steel in Isothermal Regions of a Flowing Sodium System" GEAP-4313, February, 1964.
11. Lockhart, R. W., "Sodium Mass Transfer: IX The effect of Carbon and Carbonate Additions in a Sodium Test Loop," GEAP-4436, May, 1966.
12. Pohl, L. E., "Sodium Mass Transfer: X 1963 Corrosion Sample Data," GEAP-4437, February, 1964.
13. Lockhart, R. W., "Sodium Mass Transfer: XI 1963 Test Run Reports (January-June)," GEAP-4438, February, 1964.
14. Lockhart, R. W., "Sodium Mass Transfer: XII 1963 Test Run Reports (July-December)," GEAP-4439, October, 1964.
15. Sabol, W. W., Dutina, D., Rey, D. E., and Simpson, J. L., "Sodium Mass Transfer: XIII The Determination of Total Carbon in Sodium," GEAP-4540, June, 1964.
16. Jaech, J. L., Stewart, K. B., Dunn, E. L., "Sodium Mass Transfer: XIV Statistical Analysis of 1961-1964 Sample Weight Change Data," GEAP-4830, October, 1965.

LIST OF SODIUM MASS TRANSFER PROJECT REPORTS (Continued)

17. Rowland, M. C., Plumlee, D. E., Young, R. S., "Sodium Mass Transfer: XV Behavior of Selected Steels Exposed in Flowing Sodium Test Loops," GEAP-4831, Marcy, 1965.
18. Brush, E. G., "Sodium Mass Transfer: XVI The selective Corrosion Component of Steel Exposed in Flowing Sodium," GEAP-4832, March 1965.
19. Dutina, D., Simpson, J. L., "Sodium Mass Transfer: XVII The determination of Hydrogen in Loop Sodium and Cover Gases," GEAP-4833, June, 1965.
20. Plumlee, D. E., Lockhart, R. W., Pohl, L. E., Lauritzen, T. A., "Sodium Mass Transfer: XVIII Extended Studies of Carbon Movement in Pumped Sodium Test Loops," GEAP-4834, June, 1965.
21. Rowland, M. C., Plumlee, D. E., Pohl, L. E., Lockhart, R. W., "Sodium Mass Transfer: XIX Long Term Exposure Effects in a Bimetallic 316SS-2-1/4Cr Test Loop," GEAP-4835, April, 1965.
22. Pohl, L. E., "Sodium Mass Transfer: XX 1964 Corrosion Sample Data," GEAP-4836, May, 1965.
23. Lockhart, R. W., Rowland, M. C., Pohl, L. E., "Sodium Mass Transfer: XXI 1964 Test Run reports," GEAP-4837, June, 1965.
24. Rowland, M. C., Plumlee, D. E., "Sodium Mass Transfer: XXII Metallurgical Examination of the Test Loops," GEAP-4838, October, 1965.
25. Lockhart, R. W., Blair, R. C., Dutina, D., Jaech, J. L., and Sabol, W. W., "Results of the USAEC Round-Robin Analysis for Carbon Impurity in Sodium" GEAP-4602, March, 1964.

DISTRIBUTION LIST

	<u>No. of Copies</u>
Dr. G. W. Wensch, Chief Liquid Metal Cooled Reactors Branch Division of Reactor Development and Technology U. S. Atomic Energy Commission Washington, D. C., 20545	1
R. H. Jones Liquid Metal Cooled Reactors Branch Division of Reactor Development and Technology U. S. Atomic Energy Commission Washington, D. C., 20545	1
Colonel John B. Radcliffe Director, Reactor Division San Francisco Operations Office U. S. Atomic Energy Commission 2111 Bancroft Way Berkeley, California 94704	1
Claude Pursel, Director Reactor Engineering Division Chicago Operations Office U. S. Atomic Energy Commission 9800 South Cass Avenue Argonne, Illinois 60439	1
W. H. Brummett, Jr., Director Contracts Division San Francisco Operations Office U. S. Atomic Energy Commission 2111 Bancroft Way Berkeley, California 94704	1
J. P. Holliday Reactor Division San Francisco Operations Office U. S. Atomic Energy Commission 2111 Bancroft Way Berkeley, California 94704	1
J. Dissler New York Operations Office U. S. Atomic Energy Commission 376 Hudson Street New York, New York 10014	1
C. W. Richards Canoga Park Area Office U. S. Atomic Energy Commission Post Office Box 591 Canoga Park, California 91305	1
H. W. Savage Oak Ridge National Laboratory Post Office Box Y Oak Ridge, Tennessee	1

DISTRIBUTION (Continued)

	<u>No. of Copies</u>
W. R. Simmons Argonne National Laboratory 9700 South Cass Avenue Argonne, Illinois 60440	1
Dr. W. R. Wykoff Los Alamos Scientific Laboratories Post Office Box 1663 Los Alamos, New Mexico	1
O. E. Dwyer Brookhaven National Laboratory Upton, Long Island New York	1
C. J. Klamut Brookhaven National Laboratory Upton, Long Island New York	1
J. J. Purcell Chicago Operations Office U. S. Atomic Energy Commission 9800 South Cass Avenue Argonne, Illinois 60439	1
D. T. Eggen Atomics International Post Office Box 309 Canoga Park, California	1
J. J. Morabito Atomic Power Development Associates 1911 First Street Detroit, Michigan	1
R. C. Werner Mine Safety Appliances Research Corporation Callery, Pennsylvania	1
United Nuclear Corporation 5 New Street White Plains, New York Attn: Library (For Dr. K. Goldman) Library (For J. McKee)	2
P. B. Probert N&SP Engineering Babcock & Wilcox Company Barberton, Ohio	1
Dr. John C. Woodhouse 1 Guest Lane Wilmington, Delaware	1

DISTRIBUTION (Continued)

	<u>No. of Copies</u>
C. A. Barrett National Aeronautics and Space Administration Lewis Flight Propulsion Laboratory 21000 Brookpark Road Cleveland 35, Ohio	1
Division of Technical Information Extension U. S. Atomic Energy Commission Post Office Box 62 Oak Ridge, Tennessee 37831	3
General Directorate Research and Training EURATOM Rue Belliard 51-53 Brussels, Belgium Attn: A. deStordeur	10
Dott, Ing. F. Pierantoni CNEN Via Mazzini 2 Bologna, Italy	4
Professor W. Haefele Kernforschungszentrum Karlsruhe 7500 Karlsruhe, Germany	10
Mr. G. Vendryes CEN Saclay Boite Postale 2 Gif-Sur-Yvette (S et O), France	10