DOE/ER/45293--5

DE92 017316

Annual Report

Grant DE-FG02-87ER45293

August 1, 1991 to July 31, 1992

**EFFECT OF ALLOYING ELEMENTS ON PASSIVITY AND BREAKDOWN
OF PASSIVITY OF Fe- AND Ni-BASED ALLOYS.
MECHANISTIC ASPECTS**

Submitted to

**U.S. Department of Energy
Office of Basic Energy Science
Washington, DC 20585**

By

**Z. Szklarska-Amialowska
Department of Materials Science and Engineering
The Ohio State University
Columbus, Ohio 43210**

June, 1992

MASTER

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

TABLE OF CONTENTS

Abstract	i
1. Introduction	1
2. Background	2
3. Detailed Program	24
4. Facilities	26
5. Personnel	27
6. Time and Cost	27
7. Budget	28
8. Current Support	29
9. Biographical Information	30
10. List of Publications	31-36
Appendix - Text of related papers to the proposal published by the author	
1) Structure, Composition, and Pitting Behavior of sputtered Al, Al-Cr and Al-Ta Films	37
2) Optical and Impedance Characteristics of Passive Films on Pure Aluminum	56

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

ABSTRACT

On the basis of the literature data and the current results, the mechanism of pitting corrosion of Al-alloys is proposed. An assumption is made that the transport of Cl⁻ ions through defects in the passive film of aluminum and aluminum alloys is not a rate determining step in pitting. The pit development is controlled by the solubility of the oxidized alloying elements in acid solutions. A very good correlation was found between the pitting potential and the oxidized alloying elements for metastable Al-Cr, Al-Zr, Al-W, and Al-Zn alloys.

We expect that the effect of oxidized alloying elements in other passive alloys will be the same as in Al-alloys. To verify this hypothesis, susceptibility to pitting in the function of alloying elements in the binary alloys and the composition of the oxide film has to be measured. We propose studying Fe- and Ni-alloys produced by a sputtering deposition method. Using this method one-phase alloys can be obtained, even when the two metals are immiscible using conventional methods. Another advantage to studying sputtered alloys is to find new materials with superior resistance to localized corrosion.

INTRODUCTION

The research performed on metastable aluminum alloys clearly indicates that the pitting potential of alloys is a function of the solubility of the oxides (hydroxides) of the alloying elements in acid solutions. The lower the solubility of the oxide of the alloying elements in acid solution, the higher the pitting potential of the alloy. The higher pitting potential of alloys containing Cr is often explained by the better properties of an oxide (hydroxide) film containing chromium oxide. However, the measurements of Cr in the passive film on Al-Cr alloys indicate that the chromium oxide content increases with the potential. Hence, at higher potentials, the film would be expected to be more protective than at less positive potentials. This is inconsistent with the observation that pitting occurs easier at higher potentials.

The most positive pitting potential of all the studied Al-alloys was obtained on the Al-W alloy, but W was not found in the oxide film. Mo is also absent in the oxide film formed on stainless steel and it is well known that an alloying stainless steel with Mo increases resistance to pitting.

These results contradict or weaken the hypothesis that alloying elements influence the susceptibility to pitting by altering the properties of the oxide films.

Obviously, the composition and structure of oxide films on alloys can change as a result of slow selective dissolution within the passive region of the potentials and perhaps as a result of different mobility of the cations. This process occurs faster at higher potentials and in the presence of more aggressive bulk solutions.

Chromium enrichment in the passive film on Al-Cr alloys is due to a much slower solubility of chromium oxide than aluminum oxide at a neutral pH. In contrast to the chromium oxide, the solubility of WO_3 is higher than that of the aluminum oxide at neutral pH's, hence no enrichment of W is observed in the oxide film of the alloy. Hence, the composition of the passive films on the alloys is a result of their selective dissolution characteristics in a given solution.

We are convinced that the effect of alloying elements on the pitting corrosion of other systems, i.e. on iron and nickel-based alloys is also related to the solubility of the oxide (hydroxides) of the alloying elements and the oxide of the parent metal in solid solutions. The specific role of Cl^- ion arises from its small size that allows easy penetration of the oxide film through defects in the oxide film.

We propose to verify the above hypothesis by performing measurements of the susceptibility to pitting of the Fe- and Ni-based alloys and correlate the obtained results with the solubility and composition of the passive films.

BACKGROUND

It is widely accepted that the resistance of metals to pitting corrosion is determined by the physical, electrical, and mechanical properties of the passive film. Therefore, several experiments have been performed to find the composition of oxide film on specific alloy systems that give the best results. The high resistance of stainless steel to pitting, for instance, is explained by the presence of chromium oxide on the metal surface (1). A large number of investigators have attempted to rationalize the favorable effect of Mo in stainless steel on pitting. No enrichment of Mo in the passive film has been reported in the majority

of papers written about these studies (1). Different hypotheses have been proposed to explain these observations, but are not yet satisfactory. Despite a large number of studies on the influence of alloying elements on pitting, the mechanistic influence of alloying elements on localized corrosion remains unclear.

It seems that recent experiments performed on different metastable Al-X alloys (where X is Cr, Ta, Mo, W, Zr) (2-9) are very valuable in gaining a better understanding of not only the effect of alloying elements but the mechanism of pitting corrosion as well. It was found that all of the above alloying elements, present in solid solution, significantly improve the resistance to pitting corrosion.

Using XPS to determine the composition of the film formed in a NaCl solution, it was reported that in the case of Al-Mo, Al-Cr, Al-Zr, Al-Ta alloys the passive films contain 5-10% (at) of oxidizing solute (3,4). It was also found that the concentration of the oxidized solute in the passive film depended strongly on the overpotential, increasing by a factor of approximately five from E_c (open circuit potential) to E_{np} (pitting potential) (7). However, in the case of the Al-W alloy, only at very high anodic potentials was a small quantity of WO_3 found on the surface film (7). The oxide film was reported to be very thin on Al-W (7), and Al-Ta (11), and thick on Al-Zr (3) and Al-Mo (4) alloys. According to the researchers, the thicker film on Al-Zr is less effective in blocking the transport of chloride and oxygen to the Al surface.

The authors of these works (5-7) do not offer a single explanation to account for the beneficial effect of all of the above alloying elements. For Al-Mo, Al-Cr, and Al-Ta alloys it was proposed that enhanced passivity is achieved by the oxidized solute (MoO_4^{2-} , $CrOOH$, or Ta_2O_5) which made the passive film more resistant to chloride attack due to an

electrostatic repulsion or a modification of the oxide structure. However, improved properties of Al-W alloys were interpreted as due to a synergetic interaction between W and hydrated Al_2O_3 , resulting in the formation of a more stable oxide layer at the metal-oxide interface or enhanced bonding at the metal interface. In summary, all of the above rationalization is connected with the formation of a more protective passive film on the metal surface. Therefore, the rate determining step for the localized corrosion process is ionic diffusion through the passive film.

On the other hand, Natishan et al. (10) assume that the rate determining step in pitting is adsorption of Cl^- ions on the alloy surface. They showed that a correlation exists between the pitting potential of several metals in 1N NaCl solution and the pH_{zch} (pH of zero charge) of hydrated oxides of these metals (Ta, Ti, Zr, Cu, Fe, Al, Zn, Mg). E_{np} increases with decreasing pH_{zch} . From these results it follows that pitting can occur when the oxide film covering the metal surface is positively charged, allowing Cl^- to be adsorbed. The increase in the pitting potential of ion-implanted Al-alloys has been attributed to the low pH_{zch} of the oxides of alloying elements.

Upon examination of the polarization curves (Fig. 1) it is clear that passive current density is almost identical for all supersaturated Al-alloys. It is also interesting to note that the similarity in the passive current extends over the potential range where the passive film is shown to change in composition. Therefore, it is logical to conclude that the physical and/or electrical properties of the alloy passive films are such that they are electrochemically identical (at least during the time of the measurement of the polarization curve) to the passive film on pure Al. It is likely that the defect nature and the tolerance

Figure 1: Polarization curves for elemental Al and several supersaturated Al alloys in aerated 0.1 N KCl. (7)

of the passive film on the alloys for chloride ion transport is about the same as that for a pure Al surface film. As a consequence, the rate determining step may not be associated either with the bulk characteristics of the passive film or with adsorption of Cl^- on the oxide film.

It is well established that pits can develop in chloride solutions only when acidic conditions are established within pits. Therefore, it is obvious that pit growth can proceed only when the oxide film formed on the metal surface is soluble in the acidic pit electrolyte but is only scarcely soluble in the bulk solution. It is interesting to note the correlation between the solubility of the oxidized species of the alloying element in aluminum at acidic pH, and the pitting potential. Figures 2 and 3 are a compilation of the results of E_{np} of aluminum alloys with various alloying elements in NaCl solution, obtained by different authors as a function of the solubility of the oxide of the alloying elements at pH 7 and 0. (The data taken for plotting the curves in all figures given in this paper are collected in Table 1). The lower the solubility of the oxidized species, the higher the pitting potential. This is clearly due to a much higher driving force (anodic potential) necessary to produce a low enough pH in the occluded cell to cause dissolution of the oxide film. For example, in super-saturated Al-Cr alloys, although pits may nucleate at potentials not much higher than the pitting potential of pure aluminum, they would be metastable and stop growing because CrOOH or Cr_2O_3 is stable inside the pit and would prevent further dissolution. Upon increasing the applied potential the Al dissolution rate increases and the local cell pH continuously decreases by hydrolysis, and eventually drops to the level where CrOOH is soluble, thereby giving rise to pitting. As seen in Fig. 2, the results of E_{np} vs solubility for

Figure 2: Pitting potential for non-equilibrium Al alloys in chloride solutions versus the solubility of the hydrated oxide of the alloying elements at pH 7.

Figure 3: Pitting potential for non-equilibrium Al-alloys in chloride solutions versus the solubility of the hydrated oxide of the alloying element at pH 0.

Table 1

Alloying Element	Concentration (at%)	Pitting Potential E_{np} , in V _{sce}	pH_{Zch} of the Hydrated Oxide of Alloying Element	Hydrated Oxide Listed for pH_{Zch}	Solubility of Oxidized Species of the Alloying Element (log gm.atom/l)					Oxidized Species
					(26,27)					
					pH=7	pH=4	pH=2	pH=0		
Zn	12	-0.950(22)	9.75(22)	ZnO(22)	- 1.7	4.3	8.3	12.3	ZnO.Hyd(26)	
Mg	12	-0.700 (22)	12.4(22)	MgO(22)	3	9	13	17	MgO.Hyd(26)	
Fe	4	-0.500(23)	8.5(24)	Fe ₂ O ₃ (24)	-16.1	- 7.1	- 1.1	4.9	Fe ₂ O ₃ .Hyd(26)	
Zr	4	-0.250(6)	5.9(22)	ZrO ₂ (22)	-29	-17	- 9	- 1	ZrO ₂ .Hyd(26)	
Cr	4	-0.200(6) +0.150(8)	6.25(22)	Cr ₂ O ₃ (22)	-25	-16	-10	- 4	CrOOH(4)	
Ti	7	-0.250(9)	5.0(24)	TiO ₂ (24)	-15.2	- 9.2	- 5.2	- 1.2	TiO ₂ .Hyd(26)	
Nb	5	-0.200(6)	2.8(22)	Nb ₂ O ₅ (22)	- 5.3	- 8.3	-10.3	-12.3	Nb ₂ O ₅ (26)	
Mo	4	-0.290(6)	2.0(22)	MoO ₃ (22)	3.3	0.3	- 1.7	- 3.7	MoO ₃ (26)	
W	5	0.834(7)	0.4(25)	WO ₃ (25)	0	- 6	-10	-14	WO ₃ (26)	
Al		-0.680(8)	9.1(22)	Al ₂ O ₃ (22)	-14.2	- 5.2	0.8	6.8	AlOOH(3)	

alloys containing Mo and W deviate significantly from the correlation obtained for other alloys. However, it should be noted that the solubility of Mo and W oxides are higher at pH 7 than at pH 0. Therefore, even at high anodic potentials as the pH in the occluded cell decreases, the oxides of these alloying elements remain stable resulting in a superior pitting resistance.

The hypothesis that physical, electrical, and mechanical properties of the passive film on the various non-equilibrium alloys and on pure aluminum are similar initially and the passive film possesses many defects which leads to the supposition that pit nucleation occurs as a result of metal dissolution at the metal/oxide interface. This latter suggestion has been shown to be the case in pure aluminum from studies of the electrochemical noise behavior (11). Also, the establishment of a critical pH for pitting which is specified for each alloy system, and which varies with the equilibrium solubility of the relevant surface film in acidic solutions, is the factor that stabilizes pit growth.

The time necessary for the attainment of a critical pH is seen as the induction time. Although a critical pH is necessary for stable pit growth, it is clear that unstable pit nucleation, repassivation, and hydrogen evolution reactions are continuously taking place during the pit induction period in aluminum.

Assuming that local changes in the concentration of different species within the pit arises due to transport limited processes, a quantitative prediction of such changes can be calculated by employing diffusion equations. According to Galvele (12), the minimum local current density for pit stability in a specific system is dependent on the dimensions of the defect in the metal surface that can serve as a pit nucleus. The product of this minimum

local current density (i) and a characteristic defect dimension (x) has been shown to cause the local pH within the occluded cell to attain the critical value that dissolves the passive film. The pitting potential is then the value at which defect chemistry becomes able to sustain a stable active dissolution. The smaller the diffusion path caused by the defect, the greater the pit current density required to cause stable pit growth for a specific system. The difference between the various alloy systems arises from the different values for the critical pH which in turn requires different threshold $x \cdot i$ values for stable pit growth. The lower the critical pH the higher the critical $x \cdot i$ value. The above model assumes inherent defects in the passive film permitting easy transport of the electrolyte with the aggressive anions to the metal/film interface. Also, the defects in the passive film have been suggested to serve as diffusion paths causing agglomeration of the necessary ions.

It is believed that at least a monolayer of the passive film maintains an epitaxial relationship with the metal and that the defective sites in the passive film are primarily located over the grain boundaries of the underlying metal. The passive film may also contain other defects such as pores, cracks and flaws existing over the underlying dislocations or other defects in the metal surface. It has been shown by Carter, Donald, and Saas (13) that the grain boundary thickness in Al_2O_3 is 8.5 nm. The diameters of the chloride ion and the water molecule are 0.36 (14) and 0.31 nm (15), respectively. It is therefore conceivable that both chloride ions and water can penetrate through the defective sites of the passive film with relative ease and reach the metal surface. The fact that not only the small species, H_2O , Cl^- might penetrate aluminum oxide but also CrO_4^{2-} , PO_4^{2-} (16), and MoO_4^{2-} (17) can be incorporated in the aluminum oxide indicates that this oxide is quite

defective. Hence, existence of defects on the metal surface is also a necessary condition for pit nucleation. In agreement with this supposition we expect that the pitting potential should be dependent upon the dimensions of the defect on the metal surface.

The pitting potential of metastable Al-Cr and Al-Ta alloys reported in (8) are significantly higher for the same concentration of Cr and Ta than those obtained in different works (3). This was attributed to the homogeneity and fine crystalline structure. Another proof that E_{np} depends upon the dimension of the defect are the values of E_{np} , being 300 mV more positive for sputter-deposited Al film (grain size 40nm) than for conventional Al (grain size 44 μ m). The fine grained Al film can be expected to have a smaller defect size than conventional Al (8).

It is understandable that pitting can occur only when the conditions existing on the metal surface allow for transport of Cl⁻ through the oxide film. Hence, the adsorption of Cl⁻ should not be hampered (for example, by some inhibitors which can adsorb on the metal surface more readily than Cl⁻) or by forming insoluble salts. In solutions not containing inhibitors, the transport of Cl⁻ ions will be dependent upon Cl⁻ concentration, temperature, potential and the defect size in the oxide film.

As was mentioned before, in the case of studied Al-alloys, the electrochemical properties of the passive films are independent of the composition of the alloys within the passive range. It is presumed that even in the passive region of the potential, below the pitting potential, the chloride ions and water reach the metal surface at the bottom of the defects on the oxide film and react with Al³⁺ from the metal. However, hydrolysis does not

produce enough H^+ for stable pit growth, and a corrosion product (probably aluminum hydroxide) of a different composition than the original oxide film is produced.

In our recent experiments we found localized corrosion in the passive region of the potentials (-700 mV SCE) after exposure of the a 99.999% pure Al specimen in 0.3 wt% NaCl for nine hours. A small but continuous increase of anodic current with time (from less than $0.01 \mu A$ to $0.6 \mu A$) was observed with small oscillations. Shallow 5μ sized repassivated pits were observed on the aluminum surface. All of these pits developed laterally but not in depth. It seems that after some time they became inactive. The slow monotonic increase of current indicates that the oxide film (probably that formed on pits) deteriorates continuously with time. A low value of current density within the pits (of the order $1-10 \text{ mA/cm}^2$) obtained at the pitting potential was roughly calculated.

It is necessary here to note that a correlation exists between solubility of the oxide and its pH_{zch} . Solubility of the oxides is dependent on the pH_{zch} and pH of the solution. For oxides soluble in acid solutions (line "a" on Figs. 4-6) the higher pH_{zch} the higher is its solubility in 7 to 0 pH's. For oxides stable in acid solutions (line "b" in Figs. 4-6), the lower the pH_{zch} the higher is the solubility of the oxide in neutral solutions. As pH changes from 7 to 0 the slope of line "b" alters from a negative to a positive value. At zero pH, the line "b" merges with line "a."

Because at low pH there is a simple relationship between the pH_{zch} and the solubility of oxides, it is not surprising that the pitting potential depends also on the pH_{zch} (Fig. 7). However, the composition of the oxide film formed on the alloys (for example, lack of W

Figure 4: pH of zero charge (pH_{zch}) for the hydrated oxide of alloying element versus the solubility of the hydrated oxide of the alloying element at pH 7.

Figure 5: pH of zero charge (pH_{zch}) for the hydrated oxide of alloying element versus the solubility of the hydrated oxide of the alloying element at $\text{pH} 4$.

Figure 6: pH of zero charge (pH_{zch}) for the hydrated oxide of alloying element versus the solubility of the hydrated oxide of the alloying element at $\text{pH } 0$.

Figure 7: Pitting potential for non-equilibrium Al-alloys in chloride solutions versus pH_{zch} of the hydrated oxide of the alloying element.

in the oxide film on the Al-W alloy) strongly suggests that solubility of oxides in the pit solution but not adsorption of Cl^- anions on the oxide film determines the pitting potential.

Enrichment of the solute has been observed in the passive film on Al-Cr and Al-Ta alloy films (3), but not on Al-W alloy films (7). This can be understood by considering the solubilities of the oxidized species of Cr, Ta and W at pH 7. In neutral solutions, oxidized species of Cr and Ta form stable precipitates, thereby incorporating in the passive film, while oxides of W dissolve in solutions of pH 7 and higher. Mo is not enriched in the passive film at the open circuit potential (18). However, at the applied potential, Mo in the oxide increases initially, but decreases as the applied potential is increased and approaches the pitting potential (4). As the applied potential is increased Mo^{6+} decreases and the dominant species is Mo^{4+} in a hydrated state. On the basis of these results, it is concluded that the molybdate in the passive film is probably responsible for the protective properties against pitting and that the pitting potential is a function of the Mo^{6+} concentration within the pits. However, the structure of the aluminum molybdate is not clear. MoO_2 appears to be the most stable oxide in a very narrow range of pH (4-6) and the potentials. Hence, only in specific conditions is MoO_2 responsible for improving the pitting properties. Despite the presence of Mo of different valency, a formation of insoluble aluminum molybdate could be responsible for the resistance of the Al-Mo alloy to pitting and therefore in certain conditions Mo is found in the passive film despite the high solubility of the Mo oxide in neutral solutions.

Some authors (19-21) believe that a necessary condition for stable pit growth is the presence of salt film at the pit bottom. However, we believe that the presence of a salt film is the result of a high dissolution rate within the pit and the consequent acidification. The chloride salt films (for example, FeCl_2 , NiCl_2) are stable only in highly acidic solutions. Furthermore, from the shape of the pits grown against gravity, toward gravity and sideways on stainless steel specimens, it follows that the salt film present at the bottom of the pits decreases the corrosion rate (1). Another observation that is difficult to explain by the presence of a salt film at the pit bottom is the observation of predominantly crystallographic pits on pure Al. These are often formed close to the pitting potential in dilute chloride solutions and most often on metals that produce open pits (without oxide film covering the pit).

CONCLUSION

On the basis of information given in this paper, the following mechanism of the pitting of Al-alloys and aluminum is proposed:

It is assumed that the aluminum oxide film is not an effective obstacle for penetration of chloride ions and water to the metal surface. Hence the penetration of chloride ions to the metal is not the rate determining step in pitting corrosion. The rate determining step for stable pit growth is the establishment solution composition within the preexisting defect at the metal/film interface that allows an active dissolution of the metal. This process is controlled by the dissolution rate within the defects and the diffusion (migration) of ionic species into the pit. Metastable pits are formed when the alloy/metal dissolution rate within the pits is too low to sustain a sufficiently low pH. Therefore, repassivation occurs.

Alloying elements can either cause an increase in E_{np} of Al (when the oxide of an alloying element is less soluble in acid solution than the parent metal, i.e. Cr, W oxides) or a decrease in E_{np} (when the oxide of an alloying element is more soluble than the parent metal in an acid solution). Hence, the pitting potential is the potential at which the composition of the solution within the pits is such that the passive film within the pits is unstable and a stable dissolution of the alloy occurs.

REFERENCES

1. Z. Szklarska-Smialowska, "Pitting Corrosion of Metals," NACE (1986).
2. W. C. Moshier, G. D. Davis, J. S. Ahearn, and H. F. Hough, J. Electrochem. Soc.; 133, p. 1063 (1986).
3. G. Davis, W. C. Moshier, T. L. Fritz, and G. O. Cote, J. Electrochem. Soc.; 137, p. 422 (1990).
4. W. C. Moshier, G. D. Davis, and G. O. Cote, J. Electrochem. Soc.; 136, p. 356 (1989).
5. G. D. Davis, V. C. Moshier, T. L. Fritz, G. O. Cote, G. G. Long, and D. R. Black, Annual Report MML TR 89-12 c, Martin Marietta Laboratories (1989).
6. B. A. Shaw, G. D. Davis, T. L. Fritz, and W. C. Moshier; Annual Report MML TR 90-28c, Martin Marietta Laboratories (1990).
7. G. D. Davis, T. L. Fritz, B. J. Rees, B. A. Shaw, and W. C. Moshier, Annual Report MM1 Tr 91-10, Martin Marietta Laboratories (1991).
8. R. Inturi and A. Szklarska-Smialowska, submitted for publication in J. Electrochem. Soc.
9. G. S. Frankel, M. A. Russak, C. V. Jahnes, M. Mirzamaani, and V. Brusic; J. Electrochem. Soc., 136, p. 1243 (1989).
10. P. M. Natishan, E. McCafferty, and G. K. Hubler, J. Electrochem. Soc., 133, p. 1061 (1986).

11. R. Krishnakumar and Z. Szklarska-Smialowska, "Electrochemical Methods in Corrosion Research," Helsinki (1991).
12. J. R. Galvele, *J. Electrochem. Soc.*, 123, p. 464 (1976).
13. C. B. Carter, A. M. Donald, S. L. Saas; *Phil Mag.* A 41, p. 467 (1980).
14. CRC Handbook of Chemistry and Physics, ed. by R. C. Weast, CRT Press Inc., p. F187 (1989-90).
15. A. F. Wells, "Structural Inorganic Chemistry," Oxford, Claradan Press, p. 537 (1975).
16. M. F. Abd Rabbo, J. A. Richardson, G. C. Wood, C. K. Jackson, *Corr. Sci.*, 16, p. 677 (1976).
17. B. A. Shaw, G. D. Davis, T. L. Fritz, and K. A. Olver, *J. Electrochem Soc.*, 137, p. 359 (1990).
18. W. C. Moshier, G. D. Davis, J. C. Ahern, and H. F. Hough, *J. Electrochem. Soc.*, 134, p. 2677 (1987).
19. T. R. Beck, "Advances in Localized Corrosion," NACE-9, Editors: H. S. Isaacs, U. Bertocci, J. Kruger, and S. Smialowska, p. 85 (1990).
20. G. S. Frankel, *ibid*, p. 137.
21. H. Bohni and F. Hunkener, *ibid*, p. 69.
22. P. M. Natishan, E. McCafferty and G. K. Hubler, *J. Electrochem. Soc.*, 135, p. 321 (1988).
23. M. Faas, D. Itzhak, D. Elieser and F. H. Froes, *J. Mater. Sci. Lett.*, 6, p. 1227 (1987).

24. G. A. Parks, *Chem. Rev.* 65, p. 177 (1965).
25. J. W. Diggle, *Oxides and Oxide Films*, Ed. J. W. Diggle, 2, p. 297, Marcel Dekker Inc., New York (1973).
26. M. Pourbaix, *Atlas of Electrochemical Equilibria in Aqueous Solutions*, NACE, CEBELCOR (1974).
27. *Journal of Physical and Chemical Reference Data*, 11, Suppl. No. 2, "The NBS Tables of Chemical Thermodynamics Properties," published by American Chemical Society (1982).

**DATE
FILMED**

8 / 14 / 92