"Design, Synthesis, and Characterization of Novel Fine-Particle, Unsupported Catalysts for Coal Liquefaction"

RECEIVED
JUN 11 1991
DOE/PC/90050-T2

DOE/PC/90050--T2

DE92 015536

DRAFT
Technical Progress Report

1/27/91 - 4/26/91

Michael T. Klein
Principal Investigator

Center for Catalytic Science and Technology
Department of Chemical Engineering
University of Delaware
Newark, Delaware 19716

Date Published:
May 21, 1991

Contract Number: DE-AC22-90PC90050

Prepared for Department of Energy

**U. S. DOE PATENT CLEARANCE IS NOT REQUIRED PRIOR
TO PUBLICATION OF THIS DOCUMENT**

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

MASTER

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED
42

Catalyst Synthesis

Initial synthesis work has focussed on preparation of fine-particle iron-based compounds using an $\text{Fe}(\text{CO})_5$ precursor. $\text{Fe}(\text{CO})_5$ was chosen because of the lability of the carbonyl ligands with respect to substitution under either moderate thermal or photochemical reaction conditions.

Six synthesis attempts have been carried out with $\text{Fe}(\text{CO})_5$ using CS_2 as the sulfur source. The first attempt (S-1) was made by stirring a mixture of $\text{Fe}(\text{CO})_5$ and CS_2 in heptane at reflux (98°C), but this resulted in metallic iron plating out onto the synthesis reactor walls as soon as reflux conditions were reached. The second attempt (S-2) was made at lower temperature by changing the solvent to hexane at reflux conditions (69°C). The lower temperature, however, did not prevent metallic iron from plating out when reflux conditions were reached. In the third attempt (S-3), a mixture of $\text{Fe}(\text{CO})_5$ and CS_2 was stirred in hexane at room temperature (21°C) for 1 day, after which the solution temperature was raised to 40°C and held there for 4 days. This resulted in a very low yield ($\sim 1\%$) of precipitate which, because of the low recovery, was not able to be tested. The fourth synthesis (S-4) employed ultraviolet light to photochemically promote the reaction of $\text{Fe}(\text{CO})_5$ and CS_2 . A solution of $\text{Fe}(\text{CO})_5$ and CS_2 in hexane was irradiated with longwave (365 nm) ultraviolet light for 19 hours, producing a fine, black precipitate at a yield of 10%. This synthesis was repeated twice more (S-5 and S-6) to produce enough sample for testing and characterization. The precipitate was found to be very air sensitive, which has complicated identification of the compound.

The compounds $\text{Fe}(\text{CO})_4(\text{PPh}_3)$ and $\text{Fe}(\text{CO})_3(\text{PPh}_3)_2$ have also been prepared from $\text{Fe}(\text{CO})_5$ and PPh_3 in cyclohexanol. In this synthesis (S-8), equimolar amounts of $\text{Fe}(\text{CO})_5$ and PPh_3 were added to 100 ml of distilled cyclohexanol, and the solution was

slowly brought up to 135°C and held for 2 hours. 100 ml of a hexane isomers mixture was then added and the solution was cooled to room temperature. A precipitate formed, which was then filtered and washed with additional hexane to yield 0.8 g of a pale yellow precipitate which is presumed to be a mixture of $\text{Fe}(\text{CO})_4(\text{PPh}_3)$ and $\text{Fe}(\text{CO})_3(\text{PPh}_3)_2$:

The mixture of the two compounds will be separated by vacuum sublimation and characterized and tested separately.

Catalyst Characterization

The previous attempt to characterize the catalyst synthesized from $\text{Fe}(\text{CO})_5$ and CS_2 in Tubing Bombs provided some quantitative results about the catalyst's activity. However, the conditions of the reactions were too severe to extract kinetics from the data. Dibenzyl Ether, the model compound used for testing this catalyst, was reacted without catalyst at 345°C, compared to 400°C previously. This was done in order to establish the intrinsic kinetics in an excess of Tetralin. The results of this experiment are shown in Figure 1. However, when I removed the effluent from one of the reactors, it appeared to contain small black particles, identical to those of the catalyst. This suggests that the reactor was not properly cleaned after the previous catalytic run. Figure 1 shows that the reactor which contained the old catalyst had a much higher conversion than the other reactors. Therefore,

the catalyst retained its activity after being exposed to air, tap water, soap and Methylene Chloride. This form of the catalyst appears to be robust from poisoning and decomposition due to atmospheric conditions.

Figure 1: A pseudo-first order rate law for the pyrolysis of DBE at 345 °C in an excess of Tetralin. The data point at 7 minutes corresponds to the reactor in which the fine black precipitate was found.

An identical experiment was performed, after thoroughly cleaning the reactors, to attempt to establish DBE kinetics in Tetralin at 345 °C. The results are shown in Figure 2. This experiment will be used as a baseline to which we can compare the activity of the $\text{Fe}(\text{CO})_5$ and CS_2 catalyst under the same conditions. The catalytic experiment was planned, but has been delayed due to equipment problems.

Figure 2: A pseudo-first order rate law for the pyrolysis of DBE at 345 °C in an excess of Tetralin. The rate constant is found to be $8.53 \times 10^{-3} \text{ min}^{-1}$.

Future Plans

Future plans are to test the $\text{Fe}(\text{CO})_5$ and CS_2 catalysts, as well as a $\text{Fe}(\text{CO})_4(\text{PPh}_3)$ catalyst which has been synthesized, in the Tubing Bomb Reactors. Future catalyst synthesis plans involve preparation of a variety of different iron compounds which, upon testing, should provide information relating catalyst structure and properties to reactivity with coal. Among the proposed compounds are:

**DATE
FILMED
8 / 18 / 92**