Quarterly Progress Report for the period 4/1/90 - 06/30/90

to the US Department of Energy

Project title: "Fundamental Studies of Catalytic Processing of Synthetic Liquids"

Project number: DE-FG22-89PC89783

Principal Investigator: Prof. Philip R. Watson
Department of Chemistry and Center for
Advanced Materials Research
Oregon State University
Gilbert Hall 153
Corvallis, OR 97331-4003

(503)-737-2081

Date of report: 07/30/90

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

MASTER

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

1. Background

This project revolves around understanding the fundamental processes involved in the catalytic removal of harmful oxygenated organics present in coal liquids. We will model the complex type of sulfided Mo catalyst proposed for these reactions with a simple single crystal surfaces that display a controlled range and number of reaction sites and can be extensively characterized by surface science techniques.

2. Summary

During the third quarter of this project we have studied the adsorption and thermal reaction of furan on clean sulfided Mo surfaces of various stoichiometries and structure. We have observed an unusual pyrolysis reaction pathway that appears to produce CO.

3. Work performed

During the initial months of this project we have discovered how to reliably and reproducibly produce S overlayers on a Mo(100) surface of known composition. After saturating the surface with sulfur, it can then be removed to a given point by heating. Heating to 1800K produces a clean S-free surface. We observe a number of ordered surface phases via low-energy electron diffraction (LEED) as a function of surface coverage that are in good agreement with previous studies.

We have concentrated this quarter on studying the reactions of adsorbed furan on various sulfided Mo surfaces containing 0.5 or less monolayers (ML) of sulfur. The $c(2 \times 2)$ structure adopted at 0.5ML is depicted in Figure 1. The process involves adsorbing a certain amount of furan and then observing the products that desorb into the gas phase on heating the surface over a linear temperature ramp. These products may be the original

material desorbing intact or the result of reactions on the surface. These latter are of particular interest to us.

Before we can begin such experiments we must know the form of the mass spectrum of furan measured by the quadrupole mass spectrometer in order to distinguish reaction products from cracking products formed in the ionizer. Figure 2 shows such a mass spectrum taken in our apparatus and Table I list the relative peak intensities. The parent peak occurs at 69 AMU, but the principle peak is at 39 AMU corresponding to C_3H_3 , together with C_3H_2 (38 AMU) and C_3H (37 AMU). The other half of the cracked furan molecule appears at 29 AMU (HCO) and 28 AMU (CO), although the latter peak contains a contribution from N_2 due to a small amount of residual air in the furan line.

Table I Principle peaks in the mass spectrum of furan.

m/e AMU	Intensity
14	14
29	25
37	15
38	16
39	100
40	15
42	14
68	30

Figure 2 shows an example of a temperature programmed reaction spectroscopy (TPRS) scan for 2L (2×10^{-6} torr-s) exposure of furan at -50°C to a surface that is covered with 50% sulfur. A small desorption peak due to molecular furan (39 AMU) is apparent close to room temperature, but the spectra are dominated by a hydrogen and a 28 AMU signal. The hydrogen signal bears a distinct resemblance to those reported for thiophene TPRS on sulfided Mo [1]. The 28 AMU signal is very interesting as it could originate from a number of sources - CO, N_2 , C_2H_2 or as cracking from CO_2 . We have performed a number of careful checks that indicated that this signal is in fact originating from CO resulting from reaction of furan:

- a) if the 28 AMU signal were due to ethylene, then we would expect a substantial (65%) 27 AMU peak. The 27 AMU response is within the noise.
- b) if this signal came from dinitrogen, then we would expect a 14 AMU peak at 7% of the 28 AMU intensity - this is not found.
- c) we do not observe a 44 AMU peak characteristic of CO₂.
- d) if the signal came from CO we expect 12 AMU (5%) and 16 AMU (1%) cracking products. The 16 AMU signal would be too small to observe, but the 12 AMU signal exactly parallels the 28 AMU signal.
- e) when no furan is adsorbed, there is no 28 AMU signal.

Hence, it appears that we are generating CO on the surface from furan, and that CO production occurs at several temperatures (Table II). The high temperature CO peaks are observed when CO is adsorbed on a clean or sulfided Mo surface, and is generally attributed to recombination of C and O atoms. The lowest CO peak is close to those observed for molecular desorption, but the peaks between 500-700K are quite unusual.

The amounts of each of the 2 and 28 AMU peaks vary in a systematic manner with the amount of sulfur present on the surface, as Figure 3 shows. Thus the low temperature 28 AMU peak grows as the S coverage is decreased, while the lowest temperature 2 AMU peak decreases.

At this stage it is difficult to interpret these data with confidence in terms of a reaction mechanism on the surface. Further experiments designed to probe the origin of the H₂ and CO desorption peaks are underway - e.g. using 2,5 dimethylfuran or deuterated furans. However, we note that a paper dating from 1932 recorded the production of CO

in large quantities when furan is pyrolyzed [3].

Table II Desorption temperatures for H₂ and CO on Mo after furan adsorption on sulfided Mo.

Adsorbate/ substrate	Mass (AMU)	Desorption temp (K)	Ref.
Furan/Mo-S 0.5ML	2	380	This work
		480	
		660	
	28	340	
		520	
		680	
		???	
		???	
CO/Mo-S 0.5ML	28	360	2
		820	
		950	
CO/Mo	28	475	3
		1000	
		1275	

4. Future studies

We intend to pursue the origin of the desorption peaks discussed above by suitable modifications of the adsorbate. In addition we will pre- or post-dose the surface with hydrogen to investigate the changes produced in the furan reaction on the sulfided Mo surface and more closely approach the HDO reaction.

5. References

1. M. Salmeron and G.A. Somorjai, Surface Sci. 126 410 (1983).
2. D.G. Kelly, Ph. D. Thesis, U.C. Berkeley, 1987.
3. C.D. Hurd and A.R. Goldsby, J. Amer. Chem. Soc. 54 2530 (1932).

Figure 1. Mass spectrum of furan

Figure 2. TPRS spectra of 28 and 2 AMU desorption from furan adsorbed on a Mo(100) surface at 50% S coverage.

Figure 3. TPRS spectra of 28 and 2 AMU desorption from furan adsorbed on Mo(100) surface containing various coverages of S, from about 60% (1350K) to almost 0 (1700K).

**DATE
FILMED
8/26/92**