"Design, Synthesis, and Characterization of Novel Fine-Particle, Unsupported Catalysts for Coal Liquefaction"

DRAFT Technical Progress Report

10/26/90 - 1/26/91

Michael T. Klein
Principal Investigator

Center for Catalytic Science and Technology
Department of Chemical Engineering
University of Delaware
Newark, Delaware 19716

Date Published:
February 22, 1991

Contract Number: DE-AC22-90PC90050

Prepared for Department of Energy

U. S. DOE PATENT CLEARANCE IS NOT REQUIRED PRIOR TO
PUBLICATION OF THIS DOCUMENT

MASTER

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

Introduction

The first task in our proposed study of catalysts for coal liquefaction was to prepare ultrafine dispersed metal sulfide particles by reactive precipitation from solutions of appropriate metal precursors. At this point, equipment to allow us to prepare these air-sensitive materials in an anaerobic environment has been acquired and assembled. Initial experiments aimed at synthesizing iron sulfide particles have been initiated.

As part of the investigation of short contact time catalytic coal liquefaction, initial efforts focused on the noncatalytic pyrolysis reactions of coal and a model compound, Dibenzyl ether (DBE). Two different reactor configurations were examined; catalytic experiments are planned for the coming month.

Experimental

Equipment

Glassware necessary for air-sensitive work has been assembled in the laboratory. First a manostat glove box for transfer of raw materials from their containers to the synthesis equipment, for handling the synthesized compounds, and for transfer to and from test reactors has been set up. A glove bag attached to one of the glove box entry ports acts as an air lock. The second piece of equipment is a solvent repurifier (Figure 1) for stripping oxygen and water from the solvents to be used in the syntheses. The third item is the reaction apparatus (Figure 2) in which the actual catalyst syntheses will take place. The system is equipped with a reflux condenser, thermometer, additional funnel, and direct-drive stirrer. The last item is an Ace-Burlitch inert atmosphere system, used to provide vacuum and purified (deoxygenated and dried) nitrogen to the solvent purifier and reaction apparatus.

The initial reactor configuration consisted of 4 mL Swagelok™ tubing bomb batch reactors (see Figure 3). Pyrolysis experiments were performed on both Coal (Illinois #6) and DBE in the following manner. The reactants were charged and the bomb was sealed making no effort to

remove the air from the reactor. The charged reactors were plunged into a fluidized sand bath at 400°C. The transient heat up time was three minutes. After the reaction had proceeded for the desired time, the bombs were removed from the sand bath and plunged into an ambient water bath to quench the reaction. The bombs were opened, any gases were vented and the reactor effluent was removed and analyzed. The analytical techniques employed will be discussed later in this report.

The reactor configuration discussed above was adequate as a starting point for the pyrolysis reactions, but it has shortcomings. Although ideal for single phase experiments, it falls short for two and multiphase experiments because there is no mechanism for agitation of the coal slurry to eliminate mass transfer effects, no method for running the reactor under pressure or collecting gas samples, and not a large enough sample size to perform a full and reproducible analysis of the products (2g is required for the coal runs). To accommodate these needs, a new reactor was designed. The shaker tubing bomb batch reactor is a derivative of the tubing bomb reactors used by Maa et. al. (1984) at the Exxon Research and Engineering Company. Our version is 12 ml in volume and is connected to an agitator which shakes the bomb vertically in a fluidized sand bath. Moreover, the shaker tubing bomb is fitted with Swagelok™ tubing and a needle valve which allow it to be purged and pressurized with nitrogen or hydrogen gases. This fitting also makes the collection of gas samples possible (see Figure 4). A prototype of the shaker tubing bomb has been tested successfully and more reactors presently are under construction.

Analytical

The analytical techniques utilized for the model compound studies are different from those used for the coal and coal liquids experiments. The products from the DBE pyrolysis reactions were identified using an HP 5970B mass selective detector, while the weight percents of these products were determined using an HP 5880A Gas Chromatograph with biphenyl as an internal standard.

The analytical scheme used for the coal and coal liquids is outlined in Figure 5. The reactor effluent is washed with methylene chloride and filtered. The solids then undergo an ash analysis to determine the conversion of the coal on a mass, ash-free (maf) basis. The methylene chloride solubles and liquids are then distilled using a Büchi rotary evaporator to separate the coal liquids from the methylene chloride and tetralin. The coal liquids then undergo soxhlet extractions using toluene as the solvent. The toluene solubles are extracted with hexane yielding oils (hexane solubles) and asphaltenes (hexane insolubles). Additionally, the toluene insolubles undergo soxhlet extraction with tetrahydrofuran (THF) yielding preasphaltenes (THF solubles) and THF insolubles. The mass fractions of these classes of products will be determined from the results of the extractions and the yield of gases will be calculated by difference.

Kinetic Results

A set of noncatalytic DBE pyrolysis (in tetralin) experiments were performed with the initial tubing bomb reactor configuration. The reactor effluent was analyzed and the major products were determined to be toluene, benzaldehyde and benzyl alcohol in the presence of some naphthalene (a tetralin derivative). Moreover, first order kinetics for DBE conversion were assumed, and the rate constant was regressed from the data (see Figure 6). This rate constant was 0.078 min^{-1} . This result agrees well with the rate constants provided by Cronauer (1979) and Provine (1990).

Additionally, a set of noncatalytic coal experiments (also in tetralin) were performed using the tubing bomb reactors. The mass disappearance (maf) of the coal is plotted with time (see Figure 7). This result is similar to those of Neavel (1976) for similar experiments in a dodecane (non-donor) solvent. Since the present tubing bomb reactor was not agitated, it is likely that most of the coal was not able to contact the hydrogen-donating tetralin, thus, producing results similar to those for a non-donating solvent. Soxhlet extractions on these samples currently are being performed.

A set of preliminary short time thermal coal liquefaction experiments was also performed using the shaker tubing bombs at 1000 psig of hydrogen. The mass disappearance (maf) of the

coal for this case is plotted with time (see Figure 8). These preliminary results show agreement with Neavel's data (1976) at 400°C in tetralin. This suggests that the shaker tubing bomb reactor configuration is sufficient to examine the coal liquefaction reactions in hydrogen donating solvents.

Catalyst Synthesis

Our immediate goal is to synthesize fine particle iron sulfides. Ideally these will be sol or sol-like materials that are capable of transport into the pore structure of the coal reactant, in order to carry out primary liquefaction reactions.

In order to be able to control particle size and chemical composition we have chosen to focus our initial work and experimentation on reactions of iron carbonyls including $\text{Fe}(\text{CO})_5$, $\text{Fe}_2(\text{CO})_9$, and $\text{Fe}_3(\text{CO})_{12}$. In the case of $\text{Fe}(\text{CO})_5$ carbonyl ligands exchange rapidly with incoming ligands at fairly low temperatures and also photo chemically. We hope to be able to use this characteristic to advantage in preparing iron sulfides at low temperature. The other two compounds offer similar chemistries but other pathways also open up including metal-metal bond cleavage. It is our objective to compare and contrast the results we obtain in model compound studies and experiments with coal for each of these precursors to be catalytic particles.

The first experiments that we have run have focussed upon low temperature thermal reactions of $\text{Fe}(\text{CO})_5$ and a sulfiding agent in hexane.

It is expected that under the right conditions the reaction will proceed directly to the iron sulfides but through the intermediary of a carbon-disulfide-iron carbonyl species which may be isolable and characterizable. Infrared spectroscopy will be used to follow the extent of reaction and plans are underway to employ quasi-elastic light scattering of reaction solutions to examine them for particles and sols. This experimentation has begun during the month of January and February and will continue through the next quarter. It is one of our goals to use these reactant solutions as the catalytic mechanism for batch, microscale, tubing bomb experiments with coal samples.

Plan For Future Work

In the next few months, the DBE experiments which had been performed with the first reactor configuration will be replicated in the new shaker tubing bombs. Moreover, catalytic reactions with both coal and DBE will be performed in the presence of the iron sulfide catalysts.

References

Cronauer, D.C., Jewell, D.M., Shah, Y.T., and Modi, R.J., "Mechanisms and Kinetics of Selected Hydrogen Transfer Reactions Typical of Coal Liquefaction", *Industrial and Engineering Chemistry Fundamentals*, 1979, 18, No. 2, 153-162.

Maa, P.S., Neavel, R.C., and Vernon, L.W., "Tubing Bomb Coal Liquefaction Technique", *Industrial Engineering Chemistry, Design and Development*, 1984, 23, 242-250.

Neavel, R.C., "Liquefaction of Coal in Hydrogen-donor and Non-donor Vehicles", *Fuel*, 1976, 55, 237-242.

Provine, W.D. *et al.*, "Development of a Pulse-Injection CSTR Coal Liquefaction Flow Reactor", Presented at AIChE National Conference, Chicago, IL 1990.

FIGURE 1

Figure 1: Solvent repurification apparatus for removal of traces of oxygen and moisture from solvents used in catalyst synthesis.

FIGURE 2

Figure 2: Reaction apparatus for catalyst synthesis in an air-free environment. 500 ml reactor volume suitable for preparing gram-scale quantities.

Experimental Apparatus for Tubing Bomb Reactor

FIGURE 3

Static Tubing Bomb Reactor: Charged with Reactant and Tetralin and plunged into 400°C fluidized sand bath. Assumed heat up time was four minutes. See Figures 6 and 7 for the data generated in these reactors.

Experimental Apparatus for Shaker Tubing Bomb Reactors

FIGURE 4

Shaker Tubing Bomb: Charged with Reactant, Tetralin, and 1/2" stainless steel ball bearing (for agitation), plunged into 400°C fluidized sand bath, and shaken vertically at approximately two cycles/second. Assumed heat up time was four minutes. See Figure 8 for the data generated in these reactors.

Analytical Plan for Coal Experiments

FIGURE 5

Coal Analytical Plan: The effluent from the Tubing Bombs will be analyzed according to the above flow diagram. The soxcelt extractions at each stage will be run for eight hours.

**KINETIC RATE DATA FOR DBE WITH TETRALIN
IN A TUBING BOMB AT 400°C**

FIGURE 6

DBE Kinetics: Kinetic rate data for DBE in an excess of Tetralin using a Static Tubing Bomb. Assumed first order rate law in DBE yields comparable results to published values at 400 °C.

**CONVERSION OF COAL IN TETRALIN WITH TIME AT 400°C
IN A TUBING BOMB REACTOR**

FIGURE 7

Coal Conversion: Mass conversion of coal to Methylene Chloride Solubles on a mass ash free basis.
The conversions were calculated using a low temperature ash technique.

**CONVERSION OF COAL IN TETRALIN WITH TIME AT 400°C
IN A SHAKER TUBING BOMB REACTOR**

FIGURE 8

Coal Conversion: Mass Conversion of Illinois #6 coal to Methylene Chloride Solubles on a mass ash free basis. The conversions were calculated using a low temperature ash technique

END

**DATE
FILMED**

8 / 19 / 92