NOTICE

**CERTAIN DATA
CONTAINED IN THIS
DOCUMENT MAY BE
DIFFICULT TO READ
IN MICROFICHE
PRODUCTS.**

Progress Report

SOLID ELECTROLYTES AND IMPACT-RESISTANT CERAMICS

by

C. A. Angell

Department of Chemistry

Arizona State University

August 1991

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

MASTER

CA

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

ABSTRACT

In this proposal, we describe a program to exploit recent achievements in two distinct areas of materials science, both of them dependent on the independent motion of singly charged ions through an immobile matrix. The first is the area of non-crystalline solid electrolytes in which this laboratory has gained prominence over the past decade. The second is an area proposed for study in our previous proposal and now verified as a principle worthy of considerable further investigation: it involves the use of mobile ions for fast absorption of mechanical energy from short time impacts hence inhibition of crack nucleation and failure in glassy substances. A third subject, stimulated by the DOE award to ASU for purchase of a Zeiss type 912 TEM with "Omega" type imaging energy filter, will be entered into the second or third year, if sufficient personnel funding is available. This will center on the TEM-determined charge density along ion motion channels in superionic conductors, and in critical nuclei and crystallites in crystallizing glasses.

In the first area, we will study both glassy and polymeric systems. For glassy solid electrolytes, we will perform the first electrochemical measurements of cation and anion self-diffusion coefficients in glasses, to provide data to compare with neutron scattering results and thereby to resolve a theoretical dispute. We will look for an important but so-far-unstudied relationship between conductivity/viscosity decoupling in fast ion glasses, and fragility of the liquid above the glass transition temperature. The study of structural relaxation in the glass, due to fast ion motion will then be investigated in the short-time range by photon correlation techniques for the first time, extending our timescale range for structural relaxation studies to 11 orders of magnitude. We will devote some effort to clarifying the origin of constant background loss in conducting glasses and the large differences in this loss between different glasses, and will follow up our recent suggestion that a similar background loss exists for mechanical relaxation. Finally we propose further efforts at 3D dynamic graphics studies of the fast ion transport problem.

~~In polymer-salt systems, we will perform both diagnostic and developmental studies.~~ We will try to demonstrate a continuity of behavior, as function of solvent content, between highly decoupled glass and over-coupled salt/polymer solution behavior. This will incorporate a study of polymer-salt liquid immiscibility at high temperatures to seek the relationship between salts and molecular diluent as additives to the polymer solvent. We propose also to study the effects of perfluorination on both polymer fragility and glass transition, and also on carboxylate basicity for possible improvements in overall polymer-salt performance. Finally in this section, we will use low temperature IR spectroscopy to study cation coordination sites in relation to composition.

In a separately directed study, we will endeavor to confirm exciting findings relating large increases in impact fracture resistance to timescale-matched fast ion motion, and extend the phenomenology to other systems.

Finally, we propose taking advantage of a new DOE-granted (to ASU) TEM mentioned earlier to study charge density along ion migration channels, and between atoms in homogeneously nucleating crystals in glassy matrices.

A. INTRODUCTION

It is now 13 years since the P.I., in response to a Purdue University NSF-MRL initiative, started work in the area of vitreous solid electrolytes and almost a decade since DOE initiated its support of this work. It is therefore appropriate to commence this present renewal proposal with a resume of contributions we have made to this field and to present a status report on the field. We need to take stock of progress in, and relevance of, this research area, both from the point of view of the intellectual challenge its phenomenology continues to present, and of the technological value of contributions which continued basic research may make.

This resume and stock-taking is made against a backdrop of increasing societal pressure for the nation's scientists and engineers to produce viable electrochemical power systems to replace internal combustion engines in threatened urban areas such as Los Angeles and Phoenix, and increasing frustration in applied research circles as breakthroughs in solid electrolyte research fail to materialize. The major automobile companies have all announced electric car programs,⁽¹⁾ but G.M. has said it will utilize only an advanced version of the lead acid battery which was invented a century ago, and which is well-known for its very unfavorable weight. Ford will utilize a modern system, the sodium sulfur fuel cell but one which functions only at elevated temperature and utilizes, as solid electrolyte, a sodium β - Al_2O_3 ceramic which has been plagued with mechanical failure problems. This means there will be concern about the system reliability. No company has adopted a polymer-based electrolyte although much work has been done on such systems, and many, including the present author, believe that such systems have the most promise for success in the long run. Certainly they and the related plastic crystal systems are the least exhaustively studied systems at this time.

Although hopes of easy breakthroughs may have dimmed, this does not seem the time to abandon non-crystalline solid or quasi-solid electrolyte studies. We therefore will propose, in a following section, a series of studies of both exploratory nature with respect to new systems, and of diagnostic nature on known systems, considering both polymer-based and glass-based systems. However, we will also propose a separately directed project to capitalize on some success which has greeted a new line of research in glass and ceramic fracture resistance which we initiated in our previous proposal and which we consider potentially rather important. This problem, which also intimately involves mobile ions in host matrices, will be explained at the end of the next section.

B. SCIENTIFIC BACKGROUND

1. OVERVIEW OF THIS LABORATORY'S CONTRIBUTIONS TO THE SUPERIONIC SOLIDS FIELD

Interest in fast ion conductors dates back a long time but mostly has concerned the behavior of crystalline solids. Of these, the best known examples are probably⁽²⁾ silver iodide (the high temperature phase), lithium sulfate (the high temperature phase), and CaF_2 (only one phase is known but the fast ion conducting state properties arises at high temperature by a continuous (higher order) transition). Our work, however, is focussed mostly on noncrystalline rather than crystalline materials.

The relative freedom of motion of sodium ions in glass has also been known for as long as dielectric loss has been studied, but the possibility of finding really high conductivity ($\sim 10^{-3} \Omega \text{ cm}^{-1}$) in glassy phases at room temperature is a fairly recent development.⁽³⁻¹⁰⁾ Much of the early work in this field was done abroad, particularly in Japan and Europe,^(4-8,10-16) but many of the recent successful developments have occurred in this country.⁽¹⁷⁻²⁵⁾ For the most part these studies have been centered on imaginative searches in composition space for highly conducting compositions without giving great attention to rigorous theory (although many words have been devoted to the pros and cons of "weak electrolyte" models for the conduction mechanism), or to related physical properties.

Our own work, as mentioned at the outset, was initiated in 1978 under NSF-MRL auspices. The introductory work was performed by visiting scholars Stuart Smedley⁽⁶⁾ and Leah

Boehm⁽⁷⁾ on Li⁺-conducting systems and was quickly followed by computer simulations which gave considerable detail on the motions involved.

Our belief in the importance of this work was boosted by the fine plenary lecture delivered by J. L. Souquet⁽²⁷⁾ at the 1980 2nd International Conference on Solid State Ionics at Gatlinberg, TE, (which was the second of a series of conferences which has grown out of the initial very successful international meeting on this subject held at Lake Geneva in 1979). Consequent on this stimulus and the promise of our own work, we sought and were awarded DOE support to mount a larger effort in this area. The reception given to our initial contributions to the field was quite generous and was witnessed by an invitation to the P.I. to give the plenary lecture on vitreous electrolytes⁽²⁶⁾ at the 3rd International Conference on Solid State Ionics in Grenoble, France, in 1983.⁽²⁶⁾

We will now give an overview of what we see as the useful contributions we have made under DOE support to the interesting phenomenology of this field, starting with ideas introduced in the above-mentioned plenary lecture and since developed in some detail.

The field to be reviewed in 1983 had grown enormously and included studies of both glassy solid electrolytes and rubbery polymer electrolytes.⁽²⁹⁻³²⁾ In order to organize and rationalize the information provided by some 100 research articles we introduced the dimensionless "decoupling index" suggested under a different name by Moynihan et al.^(33,34) a few years earlier as a means of comparing conductivity and viscous relaxation process in ionic liquids. This index describes the relationship between the mobilities of the "fast" ions in the glass and those particles which, below the glass transformation temperature, form the solid matrix within which the fast ions move. The decoupling index proved helpful because it allowed for a clear division between the alternative types of amorphous solid electrolyte systems under study viz., the inorganic glasses which had high decoupling indices, e.g., 10^{12} , and the salt-in-polymer electrolytes which had very low values (apparently of order unity at that time). The latter were useful as solid electrolytes only because of the very low temperatures of their glass transitions (but high temperatures of their rubber $\leftrightarrow$ liquid transitions).

Perhaps because of the utility of the decoupling index concept, as well as many experimental studies, the plenary lectureship was also requested of the P.I. for the 4th Conference in this series (held at Lake Tahoe). In this latter presentation,⁽³⁵⁾ in addition to reviewing recent developments, and pointing out the relationship between NMR relaxation observations and a.c. conductivity, we quantified the idea of a **maximum** ionic conductivity based on the experimental far infra-red spectral absorptivity, and then connected it via extrapolation to the d.c. conductivity through a regime of constant dielectric loss (or of linearly frequency-dependent conductivity). This was later (in the full report of the work⁽³⁶⁾) modified to recognize an initial high frequency ω^2 regime. Recent work from other groups particularly that of Cole⁽³⁷⁾ has now confirmed our picture (which was formerly skeptically viewed as a "fearless extrapolation"⁽³⁸⁾). The 'big picture' as it now appears to be, is shown in Fig. 1 for the case of Na₂O·2SiO₂.

Although there are few data available to judge by, it now appears that the **mechanical** relaxation associated with the fast ion motion, assessed⁽³⁹⁾ from ultrasonic⁽⁴⁰⁾ and hypersonic studies,⁽⁴¹⁾ may also exhibit an $\omega^{1.0}$ dependence with a limiting value at the lattice vibration frequency. This is shown in Fig. 2 where the data available for longitudinal mechanical relaxation in a superionic conductor (AgI)_x (Ag₂O·2B₂O₃)_{1-x} are compared with data for dielectric relaxation in a dipolar liquid. The nature of this frequency-independent loss is uncertain at this time but it is probably of fundamental importance to the understanding of glassy state dynamics.

For highly decoupled systems, of which many examples are now known, the linear regime is obliterated by an increasingly broad conductivity relaxation⁽³⁹⁾ the structural interpretation of

Figure 1 Full frequency range absorptivity/conductivity spectrum for selected ionic glasses, showing fundamental and overtone regime for a fluoride glass (zirconium-barium-lanthanum-aluminum ZBLA) and examples of good and poor conduction at room temperature.

Figure 2. Analogue of Figure 2 for absorption of mechanical energy in the same system, based on limited ultrasonic⁴⁰ and Brillouin scattering⁴¹ data. For comparison, data for absorption of electromagnetic waves by a relaxing dipolar fluid, propanediol, over the same frequency range are included. Both seem to have similar a $\sim f^{1.0}$ backgrounds over the major part of the frequency range. An Arrhenius temperature dependence for the acoustic absorption coefficient (at the frequency of the loss maximum) is a novel observation to the best of our knowledge.

which remains incompletely understood. The width of the relaxation can be characterized by the parameter β in the stretched exponential expression for the relaxation function $\phi(t)$

$$\phi(t) = \exp[-(t/\tau)^\beta]$$

which was shown by Moynihan et al.⁽⁴²⁾ to describe the process rather well. Although the fit grows increasingly poor for the more decoupled glasses, eqn. (1) remains the simplest satisfactory description available. In our most recent review (invited for a special issue of Chemical Review devoted to dynamics in condensed matter),⁽³⁹⁾ we showed that β and $\log R_\tau$ were linearly related between $\beta = 0.74$ (for the most strongly coupled system for which β is available⁽⁴³⁾) and a putative limiting value of 0.48 at the IR limit of conductivity, see Fig. 3. The correlation studied includes, equally, cationic and anionic conductors.⁽⁴³⁻⁴⁵⁾ So far this correlation, which we have attempted to interpret qualitatively in structural terms,⁽³⁹⁾ and have related to the models of Ingram⁽⁴⁶⁾ (cluster-bypass model) and Ngai⁽⁴⁷⁾ (coupling model) and Martin and Ngai,⁽⁴⁸⁾ seems to be holding up to further testing⁽⁴⁹⁾ (with some special case exceptions when conducting species are very dilute and when aqueous solutions with microheterogeneous structures are involved).

In the 1983 and 1986 reviews, we left the matter of coupling relations in salt/polymer electrolyte systems unquantified, which was unsatisfactory. In 1987, an invitation to discuss the problem at the 1st International Symposium on Polymer Electrolytes held in St. Andrews, Scotland, in 1987, prompted a first quantitative look at this question. In a paper jointly with Swedish colleague L. M. Torell (which became the opening article in the published conference proceedings⁽⁵⁰⁾), we combined data from light-scattering studies of mechanical relaxation of the Torell group with our own conductivity relaxation data to obtain the relation between local structure relaxation times and conductivity relaxation times, i.e., the decoupling index which had previously been only roughly estimated at near unity. The quantitative assessment showed that it was even smaller, typically 10^{-2} .

In our last proposal, we suggested and have now executed, a systematic series of measurements on polymer salt systems⁽⁵¹⁻⁵³⁾ with the overall aim of rationalizing the very small (subunity) decoupling indices found in these systems, and hence gaining a better understanding of the conductance mechanism.

In brief, these measurements have shown

(1) that deviations of the conductivity temperature dependence from that of the viscosity can be quantitatively accounted for by the change in populations by ion pairs with temperature as reported by Torell and colleagues⁽⁵⁴⁻⁵⁷⁾.

(2) that the ion pair population alone is quite incapable of explaining the fractional decoupling ratio, and varies in the opposite way with composition change.

(3) that the decoupling ratio increases exponentially with increasing salt content, see Fig. 4, in such a way as to rise above unity by ~14 mol% salt (86% polymer solvating groups), i.e., about where there become insufficient polymer solvating groups to complete a first coordination shell. This latter observation suggests the possibility of a continuous progression from a decoupled fast ion conducting glass (in absence of any solvent) to strongly coupled solution (in the presence of much solvent) without any great change of total conductivity, the principal effects of the polymer being the increase of coupling of the mobile species, compensated by a decrease in glass transition temperature. We will attempt, in the remainder of the current grant period, to demonstrate the possibility of such continuous transitions between the two extreme types of solid electrolytes since it would be useful, conceptually, in attempts to provide a unified treatment of the whole non-crystalline fast ion conductor field. Specific systems for study will be suggested in section C.1.(b).

Figure 3 Systematic variation of fractional exponent of Eq. (1) with decoupling ratio R_τ ($R_\tau = \tau_{\text{struc}}/\tau_{\text{cond}}$) at T_g , or conductivity at T_g .

Fig. 4. Variation of the decoupling index R_τ (log scale) with reciprocal temperature, showing rapid increases in R with decreasing solvation.

(4) that the self-diffusion coefficient of trace electroactive ions, such as Ag^+ , Tl^+ , and I^- , can be measured by chronopotentiometry or chronoamperometry, and that they probably mimic closely the behavior of the bulk ionic species, at least in the more dilute solutions. This conclusion has been reached by showing that, if an ion pair contribution to each ion diffusion coefficient is assigned on the basis of the spectroscopically determined ion pair content, then the calculated (Nernst-Einstein) conductivity is close to the measured value over a range of temperatures for each of two different reasonable choices of the ion pair mobility. According to these measurements, the cation transport number is always much smaller than the anion transport number. The anion radius calculated using the Stokes-Einstein equation

$$\eta = kT/6\pi\eta r_i$$

and the **macroscopic** viscosity, is smaller than the crystal value, as qualitatively would be expected if, as we have argued, the macroscopic viscosity is not the appropriate indicator of the friction coefficient acting on the ion. Interestingly enough, however, we find that if the **microscopic** viscosity (estimated by comparison of the shear relaxation time [calculated using the macroscopic viscosity and a Maxwell relaxation time equation] and the microscopic relaxation time estimated from Brillouin scattering), is used in the Stokes-Einstein equation, then the calculated ionic radius comes out far too large. This implies that the microscopic friction acting on the ion is much larger than estimated from the inverse local segmental mobility. The position is even more severe for the cation which has a Stokes radius larger than the crystal radius even when the **macroscopic** viscosity is used. The simplistic interpretation would be that the cation is so strongly solvated that it must drag the whole 76 repeat unit polymer chain with it as it diffuses. Since each cation is probably simultaneously solvated by ether oxygens from two or more chains, this seems improbable at least, and a more appropriate interpretation would be that the cation coordination shell is firm enough to survive numerous nearby segmental rearrangements without itself breaking up. More quantitative discussion of these results, for both dilute and concentrated solutions, will be given elsewhere. This has been a vigorous program in the hands of graduate student Mike McLin (who has now received his Ph.D. and goes to post-doc work and would like to join the auto industry in due course) and it deserves considerable follow up.

Plastic crystals.

In a partially successful attempt to blend the best features of each of the above classes of solid electrolyte systems, we attempted to develop plastic crystal fast ion conductors (PLIFICs). The basic idea was that the ordering of anions and/or some cations and/or rotator solvent molecules, would provide the solid framework—analogue to the matrix structure of the superionic glass or the entangled chains of the high molecular weight rubbery polymers. Within this matrix, it was hoped the active ions could move with relative freedom. We were, in effect, building on a principle utilized by a number of previous workers who had studied rotator phases such as the high temperature electrolyte Li_2SO_4 ⁽⁵⁴⁾, its coulombically weakened analogs like LiFeCl_4 ⁽⁵⁵⁾ and related compounds.⁽⁵⁶⁾

Two approaches, each moderately successful, were tried out. The first utilized large weak field cations with quasi-spherical anions—which showed low entropy-melting hence were rotator phases—as a base, and introduced the alkali cations by forming a double salts. An example is trimethyl methoxy methyl ammonium tetrafluoroborate lithium tetrafluoroborate double salt.⁽⁵⁷⁾ The initial contribution identified several candidate materials, the 'best' of which had a room temperature conductivity of $10^{-5} \Omega^{-1} \text{cm}^{-1}$. Another, which had been characterized calorimetrically and recommended for further study,⁽⁵⁷⁾ has since⁽⁵⁸⁾ proven to have a room temperature conductivity of $10^{-3} \Omega^{-1} \text{cm}^{-1}$, which is remarkably high. A third, prepared in a state of dubious purity but still worthy of measurement, had a room temperature conductivity of $10^{-2.8} \Omega^{-1} \text{cm}^{-1}$, though this could be due to a pervading liquid phase. Obviously these are

worthy of further consideration as solid electrolyte materials, although they have the disadvantage of being structurally feeble.

Another plastic crystal approach which has been tried is closer in concept to the salt-polymer type of system. Here the solvent itself is the plastic crystal, and we use its lattice order, rather than long chain entanglement, to provide the solid state properties. The ions are dissolved in the "solid" solvent. The potential advantage of this approach is the very low glass transition temperature which the solvent can have relative to the best polymer solvents. Of the latter, MEEP developed by Shriver and co-workers,⁽⁵⁹⁾ and a siloxane-based PEO comb polymer developed by MacFarlane and co-workers⁽⁶⁰⁾ have had the lowest T_g values (ca. 180 K) whereas T_g for the non-crystallizing rotator phase solvent formed by mixing succinonitrile and malononitrile is 115 K. Succinonitrile itself has a melting point of 65°C. The room temperature conductivity of dilute solutions of 0.1 mol% LiClO_4 in succinonitrile is $10^{-4.5} \Omega^{-1} \text{cm}^{-1}$. When the LiClO_4 content is raised to 1.25 mole%, the room temperature conductivity rises to $10^{-3} \Omega^{-1} \text{cm}^{-1}$ but this solution is thought to be partly in the liquid solution state. The conductivity rises to a high $10^{-2.5} \Omega^{-1} \text{cm}^{-1}$ by 50°C. Again, this type of system and its analogs would seem to merit further development.

2. OTHER CURRENT CONTRIBUTIONS

In other work of less global impact, but nevertheless of importance to our goal of understanding fast ion conducting solids as broadly as possible, we have carried out successful studies of mechanical relaxation in fast ion glasses at the primary (glass-forming), as well as secondary, relaxations (using a newly developed automated technique), electrical relaxation in normal and mixed ionic-electronic conductors, and calorimetric and viscosimetric studies of some unique mixed anion systems, most of which have resulted in published works.

Firstly, post-doctoral fellow Roland Bohmer, working part-time on the grant, successfully adapted a commercial automated frequency domain mechanical analyzer of limited frequency range (at only four frequencies in a two decade range) to a time-domain device which allows us to obtain very low noise relaxation functions covering 4-5 decades in time which can, if needed, be Fourier transformed to give the corresponding frequency domain spectra. The effectiveness of the method was demonstrated⁽⁶¹⁾ using the mixed $\text{AgI-Ag}_2\text{SO}_4\text{-Ag}_2\text{WO}_4$ anion superionic conductors whose interesting properties are described below. The effectiveness of this time domain method for the study of mechanical relaxation due to fast ion hopping (of which some detailed studies were made under DOE auspices at Purdue University) has not yet been properly evaluated due to temperature control problems.

Secondly, the system $(\text{LiCl})_2\text{-Li}_2\text{O} \cdot 2\text{B}_2\text{O}_3$, which has been used as the primary subject system of our study on impact fracture resistance discussed below, has been the study of a detailed frequency-dependent conductivity study by Dr. M. Tatsumisago. This work was commenced with the intention of providing the conductivity part of a two-armed project undertaken in collaboration with Professor S. W. Martin of Iowa State University who has investigated the NMR relaxation characteristics of the identical samples. Tatsumisago produced highly accurate and reproducible data covering the range from 130-330 K in the frequency range from 12 to 10^6 Hz. When presented in the Arrhenius form, the higher frequency data showed systematic departures from the d.c. conductivity plot and assumed slopes more characteristic of those obtained from the NMR studies, thus providing further evidence of the simple connection between the two types of measurement. Publication of the work has, however, been delayed until puzzling differences in the actual values of NMR and conductivity relaxation times at the same temperature have been reconciled. Since we believe both sets of measurements have been skillfully and precisely performed, and since the samples are identical, it is likely that there is something important to be learned but at this time we are not sure what the system is telling us.

Thirdly, in work initiated during a summer visiting post-doc fellowship by Prof. R. Syed at Purdue, and now continuing off campus at Norwich University under PI's guidance, we have further developed our computer simulation attack on the problem of the crossover from anionic to cationic conductivity in mixed $\text{LiF-PbF}_2\text{-Al(PO}_3)_3$ glasses⁽⁶²⁾ using, as analog system,

$\text{LiF-BaF}_2\text{-AlF}_3$.⁽⁶³⁾ The diffusivities of Li^+ and F^- under glassy conditions in the simulation, are large enough to "measure", but uncertainties are rather large so it is not yet possible to be sure that the conductivity minimum observed in the laboratory glasses is due to decrease in both cation and anion difficulties, or to an anomaly in one of them. The higher mobility of Li^+ over F^- in the LiF-AlF_3 glass has been confirmed.⁽⁶³⁾

Fourthly, analysis by grad student Hema Senapati, of differential scanning calorimetry data on the superionic conducting system $\text{AgI-Ag}_2\text{WO}_4\text{-Ag}_2\text{SO}_4$, has led to identification of a surprising "mixed oxyanion" effect⁽⁶⁴⁾ which smears out the glass transition by greatly broadening the relaxation function. Collaborative studies by her and Roland Bohmer, using the mechanical relaxation technique described above⁽⁶¹⁾ confirmed the exceptional "distribution of relaxation times." This is an interesting phenomenon and some independent work by Senapati has suggested it may be rather general. Some electron microscopic studies of crystallization products have been carried out and some papers on earlier crystallization kinetic studies performed at Purdue University under an earlier grant, have been written and accepted for publication.⁽⁶⁵⁾

Fifthly, we have recommended studies of mixed electronic/ionic conductors to try to bring to a conclusion work initiated at Purdue by Visiting Professor Kim but found to be inconclusive during preparation for publication. The new measurements, by graduate student Edwardo Sanchez, have explored a different range of oxidation states from those studied initially, and the results are different in interesting ways. The work is continuing.

Finally, during this period, the PI has written a major review of the subject of ion dynamics in glasses⁽³⁹⁾ (by invitation of Chemical Review) which sums up the position of the field at this point in time. The title page is attached.

The importance of our accumulated work on mechanical properties on glasses has been recognized in the P.I.'s invitation to be the lecturer on this subject area in an international summer school on mechanical spectroscopy being held in conjunction with the European Conference on Internal Friction and Ultrasonic Attenuation in Solids this year (September, Cracow). Last year at about the same time we were similarly honored at the Third SEATO Conference on Solid State Ionics held in Beijing (for our work on electrical properties of glasses) and this year we are invited as keynote speaker in the salt-polymer section of the Eighth International Conference on Solid State Ionics (Banff, Canada, October). Thus all aspects of our program have been granted a very pleasing degree of international recognition.

3. STATUS OF THE NON-CRYSTALLINE SOLID ELECTROLYTES FIELD

While the work described in the foregoing has been in progress, there have been many parallel developments around the world. Only some of them have been discussed in relation to our own progress and space does not permit comprehensive coverage. However, several additional, particularly relevant works will be mentioned in this section in trying to assess the state of the field.

In phenomenology, Kawamura and Shimoji⁽⁶⁶⁾ have shown how decoupling grows naturally out of different B parameters for conductivity and viscosity in the liquid state Vogel-Tammann-Fulcher equation

$$P_i = P_{0,i} \exp B_i / (T - T_0)$$

where P_i is the i th property and $P_{0,i}$, B_i and T_0 are constants. The latter is, in principle, common to all properties. The same approach explains the magnitude of quenching effects on glasses of

different conductivities. However, it contains no prescription for making B_G vanishingly small as is needed.

Comparable general approaches to polymer dynamics have been made by Ratner and colleagues,⁽⁶⁷⁾ supporting the conceptual and experimental work of Armand.⁽⁶⁸⁾

Experimental studies apparently pushing the boundary of high conductivity to its limits by incorporating the most favorable combinations of "soft" glass formers (e.g., $\text{Li}_2\text{S-SiS}_2$,⁽⁶⁹⁾ $\text{Li}_2\text{O-Li}_2\text{Se-B}_2\text{Se}_3$,⁽⁷⁰⁾ etc., mixed with the soft alkali halide LiI) have yielded excellent solid electrolytes, but none with specific conductivities reaching the values really necessary for high current density applications with long term stability. Remarkable new F^- conducting glasses have been announced⁽⁷¹⁾ but again the conductivities are not high enough. A similar situation obtains in the polymer-salt electrolyte systems. Leading workers⁽⁷²⁾ seem to have concluded that salt-polymer systems alone cannot meet requirements, and have turned to the addition of plasticizing solvents, e.g., oligomer ethers, to reduce T_g hence to increase ionic mobilities.

The recurring problem is that the conductivities needed for successful applications are approaching the theoretical limit set by the IR conductivity,⁽³⁶⁾ and the rate of approach to the limit slows down, irrespective of the variable (temperature, composition, being manipulated), as the limit is approached. It is the difficulty of obtaining the last order of magnitude in conductivity increase with unconventional systems which is forcing industry to choose either aqueous acid systems with their remarkable ambient temperature conductivities, or high temperature systems, like the sodium sulfur cell, for automobile power systems.

Although the prospects for unconventional ambient or moderate temperature auto power systems seem bleak, we do not believe enough is yet known at the fundamental level to justify stopping the search for new systems. In particular, we have not seen evidence that perfluorinated systems either as polymer materials or as low temperature molten salt or plastic crystal components, have been given adequate assessment. In the following "Proposed Work" section, we will lay out a program which will provide missing fundamental knowledge, and also plans for assessing the potential of perfluorinated systems, and other understudied materials.

Some other potential benefits of fast ion conductor research are given in the following section reviewing the novel subject of fast-ion protection of glasses against failure under impact stress.

4. IMPACT RESISTANT GLASSES AND CERAMICS

In our last proposal (1989), we introduced the idea of using the mechanical equivalent of the fast ion relaxation process on which the glassy solid electrolytes system is based, to protect glassy solids against fracture by short time scale impacts. Since impact rather than steady stress is the source of most glass failure, this concept seemed important to evaluate. The basis for it was that cracks are initiated when stress at some weakened site exceeds a critical value, and that if some mechanism can operate on a short time scale to dissipate the impact energy then the stress will not act on the nucleation site long enough to produce a crack, with consequent failure. We suggested fast ion motion could provide such a mechanism. In the past research period, we have developed a rapid and reproducible failure testing technique, which uses drawn fibers as samples, and have indeed shown that an anomalous increase in the incident energy needed to produce failure is found when the impact time scale matches the conductivity relaxation time.

In Fig. 5, we show the simple falling blade-device which we have developed to replace the miniature Kravitz pendulum tester originally purchased for this study. The fiber sample is fed through an oversize hole in a solid glass uniform diameter rod, and is impacted by a cylindrical blade (or mass 0.4-1.4 g) which falls down the rod from a pre-determined height (up to 95 cm). The height is systematically increased (changing the fiber position slightly each test so that fresh surface is impacted) until at the "final height" h_f the fiber breaks. The fiber diameter at the fracture

Fig. 5 Falling blade impact resistance tester.

xpoint, and the height of the drop are recorded and the test repeated to confirm that the "fracture initiation energy" FIE value ($FIE = mgh_f = 1/2 mv_f^2$) obtained was not the result of a particular surface or internal flaw. Normally the fracture height for neighboring fiber sections (i.e., samples of same diameter) was reproducible to within $\pm 5\%$. Surprisingly, it seemed to depend little on whether or not a fresh section of surface was impacted at each drop.

The time scale of the impact at constant impact energy can be modified somewhat by changing the mass of the blade and dropping from a greater or lesser height to obtain the same kinetic energy at impact. More will be said about time scales below.

Finally, the temperature of the measurement, hence the value of the sample internal relaxation time, can be changed by surrounding the impact site by a small heater. Temperature could be controlled to $\pm 2^\circ\text{C}$ and was varied up to 150°C . Measurements at temperatures other than ambient were awkward with the present system (due to difficult blade retrieval often each drop at high temperatures) and a thorough study of temperature effects has yet to be performed.

With the competent assistance of graduate student Q. Zheng (now post-doc at the Molecular Physics Institute in Michigan), we have used this technique to study the "specific fracture initiation energy" (SFIE) which is the kinetic energy (of the falling blade) per unit area of fiber cross section, needed to initiate a crack and thus cause failure. This quantity is assessed for each composition under study from a collection of individual fiber failure data, such as in Fig. 6, from the slope of the line passing through the **highest** energy points, since these (as in all probabilistic phenomena) are the ones most representative of the intrinsic material property.

The SFIE for a series of glass compositions in the fast ion conducting system $\text{Li}_2\text{O} \cdot 2\text{B}_2\text{O}_3 + (\text{LiCl})_2$ has been measured in this manner and is plotted in Fig. 7. Note the anomalous maximum seen at $\sim 8\%$ $(\text{LiCl})_2$. (The low point at 5% is not understood.) This is contrasted with the linear variations of T_g and density observed by Button et al.⁽⁷³⁾ for this system.

Now as the $(\text{LiCl})_2$ content increases the conductivity rises rapidly, which means the conductivity relaxation time decreases rapidly. Our thesis will be verified if the composition of maximum strength is that where the conductivity relaxation time (more correctly, the associated mechanical stress relaxation time of the glass) matches the impact time scale.

To obtain the impact time scale (approximately at this time), we have provisionally used a piezoelectric transformer in conjunction with a fast rise oscilloscope to measure the time scale in two ways. Each way uses the data produced when the blade is dropped directly onto the piezoelectric sensor. The first estimate is made directly from the half-width of the voltage-time signal recorded, see Fig. 8. The second is from the Newtonian relation between force, momentum, and time

$$F = \Delta P / \Delta t$$

We measure the force from the piezoelectric signal height (Fig. 8) and the known change of momentum from the blade mass and the velocity being reversed at impact. Both methods yield a value of $\sim 3 \times 10^{-5}$ sec. However, due to the play of the fiber in the rod orifice, our time scale should be a little longer. Conventional wisdom has suggested values of $\sim 10^{-4}$ sec, and we adopt this value pending a more thorough study with new co-workers. The conductivity relaxation time can be evaluated from the d.c. conductivity σ_{dc} using the Maxwell relation (essentially an RC circuit time equation)

$$\tau_\sigma = \frac{\epsilon_0 \epsilon_\infty}{\sigma_{dc}}$$

all of the quantities being available both from work of post-doctoral fellow H. Tatsumisago in this lab (who studied a.c. conductivity in this system, see section B.2) and from the work of Button et al.⁽⁷⁴⁾

Fig. 6. Energy needed to fracture fibre as function of fibre cross section area, for two borate glasses. The slope of the line drawn through the extreme points is taken as the "specific fracture initiation energy" SFIE for the glass.

Time scale of impact

Remember time and force scales have arbitrary baselines, only ΔF and Δt count
 timescale is either time width at half maximum (width at baseline would also be possible)
 by using Newton's first law $F = m \frac{\Delta v}{\Delta t}$ (this is the standard)
 with $v = \sqrt{2gh}$ $\rightarrow \Delta t = \frac{m \sqrt{2gh}}{F}$

Force is measured in Voltage $1V = 25.5 \mu N$

	h/cm	m/g	$\Delta F/V$	$\Delta t/\mu s$	time scale μs
①	22.2	1.222	3.4 ± 0.2	18.4 ± 1	22 ± 3
②	18.2	1.222	1.2 ± 0.15	26.2 ± 4	26 ± 3
	22.2	0.331	0.6 ± 0.05	25.5 ± 3	16 ± 1
③	12.2	0.331	0.17 ± 0.04	44.0 ± 7	22 ± 2

Result of time scale
 (1) on next page

Result: timescale $(30 \pm 20) \mu s$

Note: Time scale smaller for larger height (i.e. larger velocity at impact)

Fig. 8. Determination of impact time scale by piezoelectric technique.

Fig. 9

The conductivity relaxation time is shown as a function of composition in Fig. 9. The horizontal line in the figure marks the impact time scale in our experiment. We note, with great satisfaction, that it cuts the conductivity relaxation time plot essentially at the composition of the SFIE anomaly maximum.

This would appear to thoroughly vindicate our initial idea and to set the stage for a feature program in this area. The data on the temperature dependence of the FIE for pure $\text{Li}_2\text{O} \cdot 2\text{B}_2\text{O}_3$ would also seem consistent with it, but an anomaly at the actual temperature where

$\tau_G \approx 3 \times 10^{-4}$ s has not been directly demonstrated because data were obtained at only three temperatures, and were obtained before we knew where to look. This and other studies related to exploiting our initial success are described in the second part of the proposed work section (C.2).

5. REFERENCES FOR SCIENTIFIC BACKGROUND

1. (a) Arizona Republic Section C, May 26, 1990. (b) Industry Reports.
2. (a) *Fast Ion Transport in Solids*, Ed. Vashishta, North Holland, (1979) (Proceedings of Lake Geneva conferences). (b) *High Ionic Conductivity in Solid Ionic Conductors*, Ed. T. Takahashi, World Scientific, Singapore, 1989.
3. Evstrop'ev, K. K., Veksler, G. I. and Kondrat'eva, B. S., Dokl. Akad. Nauk. SSR 215 (1974) 902.
4. Magistris, A., Chiodelli, A. and Schiraldi, A., Electrochim. Acta 19 (1974) 665; 24 (1980) 256.
5. Minami, T., Takuma, V., and Tanaka, M., J. Electrochem. Soc. 124 (1977) 1660.
6. Minami, T., Nambu, H. and Tanaka, M., J. Am. Ceram. Soc. 60 (1977) 283.
7. Malugani, J. P., Wasniewski, A., Doreau, M., Robert, G. and Al Rikabi, A., Mat. Res. Bull. 13 (1978) 427.
8. Audier, M., Ravaine, D. and Souquet, J.-L., C. R. Acad. Sc. Paris 282C (1976) 499.
9. Kawamoto, Y., J. Non-Cryst. Sol. 20 (1976) 393.
10. Smedley, S. I., Angell, C. A., Sol. St. Commun. 27 (1978) 21.
11. Grant, R. J., Ingram, M. D., Turner, L.D.S. and Vincent, C. A., J. Phys. Chem. 82 (1978) 2838.
12. Robert, G., Malugani, J. P. Saida, A., Solid State Ionics (Netherlands) 3-4 (1981) 311.
13. Carette, B., Ribes, M., Souquet, J. L., (1983)
14. Ribes, M., Barran, B. and Souquet, J. L., J. Non-Cryst. Sol. 38-39 (1980) 271.
15. Malugani, J. P. and Robert, G., Mat. Res. Bull. 14 (1979) 1075.
16. Leroy, D. and Ravaine, D., C. R. Acad. Sci. Paris 286C (1978) 413.
17. Button, D. P., Tandon, R. P., Tuller, H. L. and Uhlmann, D. R., Sol. State Ionics 5 (1981) 655.
18. Susman, S., Boehm, L., Volin, K. J. and Delbecq, C. J., Solid State Ionics 5 (1981) 667.
19. Kennedy, J. H. and Yang, Y., J. Solid State Chem. 69, 252 (1987).
20. Susman, S., Boehm, L., Volin, H. J. and Delbecq, C. T., Solid State Ionics 5, 667 (1981).
21. Kennedy, J. H. and Zhang, Z., Solid State Ionics 28/30, 726 (1988).
22. Liu, C. and Angell, C. A., Solid State Ionics 13, 105 (1984).
23. Liu, C., Sundar, H.G.K., and Angell, C. A., Mat. Res. Bull. 20, 525 (1985).
24. Martin, S. W., Mater. Chem. Phys. 23, 225 (1989).
25. Shelby, J., J. Am. Ceram. Soc. 68, 551 (1985).
26. Boehm, L. and Angell, C. A., *Proc. of Fast Ion Transport in Solids Conference*. Lake Geneva, Wisconsin, Eds. P. Vashishta, J. N. Mundy and G. K. Shenoy, Elsevier North Holland, Inc., (1979) p. 719.
27. Souquet, J. L., Solid State Ionics 5 (1981) 77.
28. Angell, C. A., Solid State Ionics 9 & 10, 3 (1983).
29. Armand, M. B., Chabagno, J. M. and Duclot, M. J., *Fast Ion Transport in Solids* (North Holland, Amsterdam, 1979) p. 131.
30. Shriver, D. F., Papke, B. L., Ratner, M. A., Dupon, R., Wong, T. and Brodwin, M., Solid State Ionics 5 (1981) 83.
31. Papka, B. L., Ratner, M. A. and Shriver, D. F., J. Electrochem. Soc. 49, 1694 (1982).
32. Killas, A., LeNest, J. F., Cheradame, H. and Gandini, A., Makromol Chem. 183, 2835 (1982).
33. Moynihan, C. T., Balitactac, N., Boone, L. and Litovitz, T. A., J. Chem. Phys. 55 (1971) 3013.
34. Ambrus, J. H., Dardy, H. and Moynihan, C. T., J. Phys. Chem. 76 (1972) 3495.
35. Angell, C. A., Cheeseman, P. A. and Kadiyala, R. R. Chemical Geology, 62, 85-95 (1987).
36. Liu, Changle and Angell, C. A. J. Chem. Phys., 93, 7378 (1990).
37. Burns, A. V., Cole, R. H., Chryaschoas, G. and Risen, W., Phys. Chem. Glasses 30, 264 (1989).
38. Cole, R. H., Ann. Rev. Phys. Chem., 40, 2 (1989).

39. Angell, C. A. Chem. Rev., 90, 523 (1990).
40. Carini, G., Cutroni, M., Federico, M., Galli, G. and Tripodo, G., Phys. Rev. B30, 7219 (1984); B32, 8264 (1985).
41. Borjesson, L., Phys. Rev. B36, 4600 (1987).
42. Moynihan, C. T., Boesch, L. P. and Laberge, N. L., Phys. Chem. Glasses 14, 122 (1973).
43. Howell, F. S., Bose, R. A., Macedo, P. B. and Moynihan, C. T., J. Phys. Chem. 78, 639 (1974).
44. Etienne, S., Cavaille, Y., Perez, J. and Johari, G. P., Philos. Mag. 51, L35 (1988).
45. Kulkarni, A. R., Sundar, H.G.K., and Angell, C. A. Solid State Ionics, 24, 253-257 (1987).
46. Ingram, M. D., Mater. Chem. Phys. 23, 51 (1989).
47. Rendell, R. W., Ngai, K. L., Fong, G. R. and Aklonis, J. J., Macromolecules 20, 1070 (1987).
48. Ngai, K.L. and Martin, J.W., Phys. Rev. B, 40, 10, 550 (1989).
49. C. T. Moynihan (private communication).
50. Torell, L. M. and Angell, C. A., Polymer J. (Proc. 1st International Conference on Polymer Electrolytes), British Polymer Journal, 20, 173 (1988).
51. McLin, M. C. and Angell, C. A., J. Phys. Chem. (in press).
52. McLin, M. C. and Angell, C. A., Solid State Ionics, (1992) (submitted).
53. McLin, M. C. and Angell, C. A., Solid State Ionics, (submitted).
54. Aronsson, R., Jansson, B., Knape, H. E. G., Lunden, A., Nilsson, L., Sjoblom, C. A. and Torell, L. M., J. de Phys. Colloq. C6, 41, 6 (1980).
55. Weppner, W. and Huggins, R. A., J. Electrochem. Soc. 124, 35 (1975); Phys. Lett. 58A, 245 (1976); Solid State Ionics 1, 3 (1980).
56. Cros, C., Hanebali, L., Latié, L., ViMeneuve, G. and Gang, W., Solid State Ionics 10, 139 (1983).
57. Cooper, E. I. and Angell, C. A., Solid State Ionics 18&19, 570 (1986).
58. List, D. L. and Angell, C. A. (to be published).
59. Dupon, R., Papke, B. L., Ratner, M. A. and Shriver, D. F., J. Electrochem. Soc. 131, 586 (1984).
60. MacFarlane, D. R. (private communication).
61. Böhmer, R., Senapati, H. and Angell, C. A., J. Non-Cryst. Sol. 131-133, 182 (1991).
62. Kulkarni, A. R. and Angell, C. A., J. Non-Cryst. Sol., 99, 195 (1988).
63. Syed, R. and Angell, C. A., (to be published).
64. Senapati, H. and Angell, C. A., J. Non-Cryst. Sol., 130, 58 (1991).
65. (a) Senapati, H. and Angell, C. A., J. Am. Ceram. Soc. 74, 000 (1991). (b) P.L. #.271.
66. Kawamura, J. and Shimoji, M., J. Non-Cryst. Sol. 88, 295 (1986).
67. (a) Ratner, M. A., *Polymer Electrolytic Reviews I*, Eds. J. R. MacCallum and C. A. Vincent, Elsevier, London, 1987, P. 173. (b) Ratner, M. A. and Nitzan, A., Faraday Disc. Chem. Soc. 88, 19 (1989).
68. Armand, M., in *High Ionic Conductivity in Solid Ionic Conductors*. Ed. T. Takahashi, World Scientific, Singapore, 1989, p. 114.
69. Zhang, Z. and Kennedy, J. H., Solid State Ionics 28-30, 726 (1988).
70. Martin, S. W., Mater. Chem. Physics, 23, 225 (1989).
71. (a) Kawamoto, Y. and Nohara, I., Solid State Ionics, 22, 207 (1987). (b) Kawamoto, Y., Fujiwara, J., Hirao, K. and Soga, N., J. Non-Cryst. Sol, 95/96, 921 (1987).
72. Huq, R., Koksband, R., Tønder, P. E. and Farrington, G. in *Recent Advances in Fast Ion Conducting Materials and Devices*. Eds. Chowdari, B. V. R., Lin, Q. and Chen., L., World Press, Singapore (1990) p. 63.
73. Button, D., Ph.D. thesis, M.I.T. (1984).
74. Button, D. P., Mason, L. S., Tuller, H. L. and Uhlman, D. R., Solid State Ionics, 9&10, 585 (1983).

END

**DATE
FILMED**

7 / 21 / 92