NOTICE

**CERTAIN DATA
CONTAINED IN THIS
DOCUMENT MAY BE
DIFFICULT TO READ
IN MICROFICHE
PRODUCTS.**

DOE/PC/88856--T6

DE92 016139

Quarterly Technical Progress Report No. 6
For Period
May 1 through July 31, 1989

SURFACE MAGNETIC ENHANCEMENT FOR COAL CLEANING

Submitted to:

U.S. Department of Energy
Pittsburgh Energy Technology Center
P.O. Box 10940
Pittsburgh, PA 15236

Contract Number: DE-AC22-88PC88856

Technical Program Officer: McMahan L. Gray

Prepared by:

Project Manager and Principal Investigator
J. Y. Hwang
Program Manager - Minerals

Institute of Materials Processing
Michigan Technological University
Houghton, Michigan 49931

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

MASTER

SUMMARY AND FUTURE WORK

The fundamental chemistry for selective adsorption of magnetizing reagent on coal-associated minerals to enhance the magnetic susceptibility of minerals have been established in Phase I study. The application of the results on coal cleaning is in progress in the Phase II study. The task in Phase II study for coal selection, preparation, and characterization is completed in this reporting period. The optimization of adsorption conditions for -48 mesh ROM coals and flotation concentrates is about completed. Experiments have shown that successful coal cleaning can be obtained with this magnetizing reagent approach. The task to adapt the approach to various processing schemes is just initiated.

The major work for the next quarter will be further optimization of adsorption conditions and the adaptation of the magnetizing approach to various coal cleaning processes.

INTRODUCTION

This research studies the surface enhancement of magnetic susceptibility of minerals for coal cleaning by adsorbing magnetizing reagent on minerals. The objectives of the study include: (i) to define the optimal conditions of adsorption selectivity and magnetic enhancement for magnetizing reagents, (ii) to determine the effect of such magnetic enhancement on the coal cleaning efficiency with magnetic separations, and (iii) to evaluate where this method can be adapted to the existing coal processing schemes for maximum effectiveness.

Three phases of work are included in this research: a fundamental study, an application study, and an industrial laboratory study. The fundamental study investigates the basic chemistry involved in the interactions of magnetizing reagents and minerals. The application study will apply the basic chemistry for coal cleaning under various process schemes. The work performed during this reporting period is part of the application study. Major efforts are on coal selection, preparation and characterization (Task 6) and optimization of magnetizing conditions (Task 7).

PROGRESS BY WORK BREAKDOWN STRUCTURE

Task 1. Magnetizing Reagent Preparation.

Thirty five magnetizing reagents with various surfactant functional groups have been prepared for this study. The properties of these reagents were documented in the previous reports. Five reagents, selected from

different cationic, anionic, and nonionic categories, were investigated for their shelf life. The results show that magnetizing reagents are stable for long term storage. This task is completed.

Task 2. Mineral/Reagent Interactions.

The interactions of magnetizing reagents and minerals under various conditions have been investigated. The conditions include pH, kinds and dosages of magnetizing reagents, mineral activator, coal depressant, oxidation effect, and slurry regulators. All of the experimental results have been described in the previous reports. This task is completed.

Task 3. Magnetite Size Effect.

The particle size of magnetite and its effects on the properties of magnetizing reagents were studied. The experiments have been completed and the results were described in the previous reports. This task is completed.

Task 4. Phase I Data Evaluation.

All of the results in Phase I study have been evaluated. The most promising conditions for selective magnetic enhancement of coal-associated minerals have been selected.

Task 5. Phase I Report and Review.

The reports documenting the progress in Phase I study have been completed and reviewed.

Task 6. Coal Selection, Preparation, and Characterization.

Selection and Preparation. Three coals are selected for the Phase II study. They are Illinois No. 6, Ohio Lower Kittanning, and West Virginia Pocahontas seams. Each 400 pound sample was cut from freshly mined 4" x 0" coal and shipped in sealed containers.

The preparation procedures and weight splits for each coal can be found in Figure 1 through Figure 3. The as received sample was blended three

times then cone and quartered to produce a reserve sample and a sample which was crushed to 3/4-inch. The minus 3/4-inch sample was riffled to yield a fraction for reduction to minus 48 mesh and a second fraction for screening at 6 mesh and 48 mesh. The crushed minus 48 mesh material was then split into a reserve sample, a head sample, and a testing sample (300 grams per charge). The other minus 3/4-inch fraction was screened as indicated above to make a 3/4-inch by 6 mesh fraction for heavy media testing, a 6 mesh by 48 mesh fraction for tabling and a 48 mesh by 0 for flotation. All samples are stored in plastic bags which were filled and sealed in an argon atmosphere. In addition the plastic bags are stored in either 55-gallon drums or 5-gallon plastic pails which were evacuated then filled with argon. To insure low levels of oxygen in the storage containers each was evacuated to 15-ins. of Hg and filled with argon four times.

Flowsheets for the heavy media, tabling, and flotation tests on the three coals are shown in Figure 4 through 6 respectively. The heavy media concentration was done in an Erickson 10-inch cone using magnetite media at gravities of 1.3 and 2.0. Concentration of the 6 mesh by 48 mesh was done on a Deister No. 15s laboratory concentrating table with a coarse deck. All of the flotation work was done in a Wemco laboratory flotation machine at 12% solids. A combination of 1/3 Dowfroth 250 and 2/3 No. 2 fuel oil by weight was utilized as the frother/collector.

The data on weight splits, assays of the products, and a comparison of calculated and assayed head analysis are also shown in Figure 4 through Figure 6. The heavy media concentration tests reduced the ash contents of Illinois No. 6, Lower Kittanning and Pocahontas from 19.17%, 4.13% and 43.03% to 4.79%, 2.16% and 3.32%, respectively, at 1.3 specific gravity.

The sink fractions of the three coals at 2.0 specific gravity contain 62 to 90% ash. The middlings, which have specific gravities between 1.3 and 2.0, have ash contents of 22.17%, 14.61%, and 21.63%, respectively, for the three coals.

The tabling process reduces the ash contents of the three coals from 19.39%, 7.89%, and 16.27% to 6.69%, 2.33%, and 4.11%, respectively. The tabling refugees of the three coals have ash contents in the range of 25% to 50%. Flotation concentrates have the ash contents of 10.61%, 9.97%, and 5.58%, respectively, for the three coals. The flotation refugees contain ash in the range of 63% to 78%.

Pyritic sulfur is reduced to below 0.5% by heavy media and tabling processes. Flotation is not as efficient as these processes in pyritic sulfur removal.

Characterization. The head samples of each coal were analyzed for moisture, volatile matter, fixed carbon, ash, total sulfur, sulfate sulfur, pyritic sulfur, and heat of combustion. Table 1 shows the data for the three coals.

The grindability of each coal was established with a standard procedure. The test was conducted using a laboratory stainless steel rod mill (7" I.D. x 9" long). About 300 grams of minus 48 mesh coal at 25% solid content was ground in each test. Soda ash (2 lb/ton) and sodium tripolyphosphate (1 lb/ton) was added for dispersion. The pH was set at 9 by NaOH or HCl. Grinding times were 20, 40, 60, and 80 minutes. The size distributions were determined with a Microtrac. The results are shown in Figure 7 through Figure 9.

The washability of the -48 mesh sample was carried out with the heavy liquid tests. Commercially available CERTIGRAV (American Minechem Corp.) heavy liquids were utilized. A high speed centrifuge was employed to enhance the separation of sink and float products at the specific gravities ranging from 1.3 to 1.95. Surfactants were added to insure the wetting and dispersion of particles. The results of these tests are plotted on Figure 10.

The mineralogy was performed using the x-ray diffraction methods. The sink material from 1.95 heavy liquid test was utilized. The diffraction patterns of the three coals are shown in Figures 11 through 13. The minerals corresponding to the diffraction peaks were identified and listed on these figures. The major minerals in Illinois No. 6 seam are quartz, clays, pyrite and calcite. Clays include kaolinite, chlorite and muscovite. The major minerals in Lower Kittanning are quartz, pyrite, feldspar, hematite, and chlorite. Pocahontas seam has the major minerals of quartz, muscovite, chlorite, kaolinite, feldspar, calcite, and little siderite and gypsum (anhydrite). Pyrite is rare.

Task 7. Optimization of Magnetizing Conditions.

In the Phase I study, ten conditions have been identified for the selective adsorption of magnetizing reagents on coal-associated minerals. These conditions are evaluated in this study to determine if they are applicable for various coals. In addition to the ten conditions, another condition was added to the study. The results of Phase I study have led to the development of a hypothesis that selective coal depressing may be achieved by modifying coal surface hydrophillic. Cations have been proved the major activators of hydrophobic coal. After modifying coal surface hydrophillic, the enrichment of cations on coal surface will be eliminated and thus will not adsorbing the magnetizing reagent.

Table 2 shows the results of separation of Illinois No. 6 coal at -48 mesh using the hydrophillic approach. Six magnetizing reagents, which include anionic, nonionic and cationic types, were evaluated. They are MR-1 (cationic), MR-45 (nonionic), MR-58 (anionic), MR-60 (anionic), MR-146 (cationic), and MR-211 (cationic). MR-146 and MR-211 are new reagents introduced for this study. The dosage of the magnetizing reagents was set at about 2 pounds of magnetite per ton of coal. Magnetic separation was carried out at 5 kilogauss (0.5 tesla). Tap water was utilized in these tests. The pH of slurry is in the range of 7 to 8 without adjustment. The separation results show that the hypothesis is valid. The ash content in the magnetic fraction is always above 40% while that in the nonmagnetic concentrate is reduced from 22% to about 10%. Cationic type magnetizing reagent is more effective than the nonionic and anionic type magnetizing reagent. MR-146 appears to be the most effective one. Further improvement in the grade and recovery is definitely possible because both the chemical and separation conditions have not been optimized. Misplacement of coal particles in magnetics and mineral particles in nonmagnetics have been verified under the microscope. These problems will be investigated in the separator studies.

To determine whether the hydrophillic approach can be applied on various coals, the separation tests were also conducted on Lower Kittanning and Pocahontas coals. Table 3 shows the results using MR-146. The ash contents of Lower Kittanning and Pocahontas are reduced from 6.65% and 29.98% to 2.52 and 11.31%, respectively.

The flotation concentrate of the three coals was investigated with the same approach. As shown in Table 4, all the results indicate that the flotation concentrate at -48 mesh can be further cleaned with the

magnetizing reagent approach. With optimization, it may be possible to concentrate the unliberated particles from the flotation concentrate to avoid cost fine grinding for coal cleaning.

The comparison of the hydrophillic approach with the ten conditions identified in the Phase I study on the cleaning of coals can be found in Table 5. Although the ten conditions also show promising separation results, the hydrophillic approach undoubtedly yields the best performance. Therefore, the subsequent studies will be focused on the hydrophillic approach.

SAMPLE PREPARATION FLOWSHEET

ILLINOIS #6 COAL SAMPLE

HEAD ANALYSIS

HEAT OF COMB 6023.2 CAL/G
 TOTAL SULFUR 3.94%
 PYRITIC SULFUR 1.56%
 SULFATE 0.04%
 ORGANIC SULFUR 2.34%
 ASH 22.44%
 FIXED CARBON 45.97%
 VOLATILES 31.02%
 MOISTURE 0.57%

SAMPLE PREPARATION FLOWSHEET

LOWER KITTANING SAMPLE

HEAD ANALYSIS

HEAT OF COMB 7708 CAL/G
 TOTAL SULFUR 2.43%
 PYRITIC SULFUR 1.39%
 SULFATE 0.07%
 ORGANIC SULFUR 1.03%
 ASH 6.37%
 FIXED CARBON 53.01%
 VOLATILES 39.29%
 MOISTURE 1.33%

SAMPLE PREPARATION FLOWSHEET

POCAHONTAS #3 COAL SAMPLE

HEAD ANALYSIS

HEAT OF COMB 6166 CAL/G
 TOTAL SULFUR 0.75%
 PYRITIC SULFUR 0.43%
 SULFATE 0.07%
 ORGANIC SULFUR 0.25%
 ASH 27.55%
 FIXED CARBON 58.49%
 VOLATILES 13.59%
 MOISTURE 0.37%

CONCENTRATION FLOWSHEET

ILLINOIS #6 COAL SAMPLE

CONCENTRATION FLOWSHEET

LOWER KITTANNING COAL SAMPLE

CONCENTRATION FLOWSHEET

POCAHONTAS #3 COAL SAMPLE

ASSAY HEAD

100% WEIGHT
27.55% ASH
0.75% TOT SULFUR
0.43% PYR SULFUR

CALCULATED HEAD

100% WEIGHT
30.96% ASH
0.67% TOT SULFUR
0.28% PYR SULFUR

Figure 7. Size distribution of Illinois No. 6 coal at various grinding times.

Figure 8. Size distribution of Lower Kittanning coal at various grinding times.

Figure 9. Size distribution of Pocahontas coal at various grinding times.

Figure 10. Washability of three coals.

Figure 11. X-ray diffraction pattern and mineral interpretation of Illinois No. 6 coal.

Figure 12. X-ray diffraction pattern and mineral interpretation of Lower Kittanning coal.

Figure 13. X-ray diffraction pattern and mineral interpretation of Pocahontas coal.

Table 1. Head analyses of the test coals.

	<u>Illinois</u> <u>No. 6</u>	<u>Ohio Lower</u> <u>Kittanning</u>	<u>W. Virginia</u> <u>Pocahontas</u>
Moisture %	0.57	1.33	0.37
Volatiles %	31.02	39.29	13.59
Fixed Carbon %	45.97	53.01	58.49
Ash %	22.44	6.37	27.55
BTU/lb	10,851	13,886	11,108
Total S%	3.94	2.43	0.75
Sulfate S%	0.04	0.07	0.07
Pyritic S%	1.56	1.39	0.43

Table 2. Magnetic separation of Illinois No. 6 coal at -48 mesh with various magnetizing reagents.

<u>Magnetizing</u> <u>Reagent</u>	<u>Fraction</u>	<u>Wt %</u>	<u>Ash %</u>
MR-1 (cationic)	Nonmag	76.30	12.11
	Mag	23.70	41.78
	Calc. Head		19.14
MR-45 (nonionic)	Nonmag	77.94	12.95
	Mag	22.06	41.66
	Calc. Head		19.28
MR-58 (anionic)	Nonmag	72.77	11.68
	Mag	27.23	42.71
	Calc. Head		20.13
MR-60 (anionic)	Nonmag	78.76	13.68
	Mag	21.24	42.17
	Calc. Head		19.73
MR-146 (cationic)	Nonmag	69.67	9.75
	Mag	30.33	42.06
	Calc. Head		19.55
MR-211 (cationic)	Nonmag	71.21	11.09
	Mag	28.79	41.29
	Calc. Head		19.78

Table 3. Magnetic separation of three coals at
-48 mesh with surface enhancement.

	<u>Illinois No. 6</u>	<u>Lower Kittanning</u>	<u>Pocahontas</u>
Nonmag Ash %	9.75	2.52	11.03
Mag Ash %	42.06	21.33	59.00
Nonmag Wt %	69.67	78.06	60.49
Mag Wt %	30.33	21.94	39.51
Calc. Head Ash %	19.55	6.65	29.98

Table 4. Magnetic separation of flotation concentrates
at -48 mesh with surface enhancement.

	<u>Illinois No. 6</u>	<u>Lower Kittanning</u>	<u>Pocahontas</u>
Nonmag Ash %	5.87	5.42	3.36
Mag Ash %	15.47	20.19	14.96
Nonmag Wt %	57.90	71.03	85.68
Mag Wt %	42.10	28.97	14.32
Calc. Head Ash %	9.91	9.70	5.02

Table 5. Magnetic separation of coals with various enhancement conditions at -48 mesh.

		Illinois No. 6		L. Kittanning		Pocahontas		Magnetizing Reagent No.	Coal Depressant	Mineral Activator	pH
		Nonmag	Mag	Nonmag	Mag	Nonmag	Mag				
Ash Z	9.75	42.06	2.52	21.33	11.03	59.00		MR-146	hydrophillic		7
Wt Z	69.67	30.33	78.06	21.94	60.49	39.51					
Ash Z	15.12	32.32	3.75	15.39	15.93	43.13		MR-60	Na ₂ S	CaCl ₂	7
Wt Z	67.43	32.57	84.06	15.94	51.12	48.88					
Ash Z	16.89	29.95	4.51	14.05	18.81	38.43		MR-30	Na ₂ S		7
Wt Z	67.35	32.65	82.73	17.27	47.31	52.69					
Ash Z	15.68	35.28	4.25	18.57	14.18	56.13		MR-30	humic acid	CaCl ₂	7
Wt Z	76.83	23.17	86.29	13.71	64.95	35.05					
Ash Z	15.68	35.90	3.59	16.37	15.45	50.66		MR-1	molasses		7
Wt Z	74.54	25.46	80.28	19.72	59.76	40.24					
Ash Z	16.34	30.93	4.36	14.62	20.38	39.93		MR-45	Na ₂ S		9
Wt Z	69.36	30.64	79.90	20.10	53.07	46.93					
Ash Z	16.69	30.29	4.25	15.38	15.18	51.45		MR-58	Na ₄ P ₂ O ₇		7
Wt Z	75.98	24.02	81.40	18.60	61.93	38.07					
Ash Z	16.47	31.44	4.77	21.24	15.83	52.12		MR-58	Na ₃ PO ₄	FeSO ₄	7
Wt Z	68.78	31.22	83.97	16.03	61.34	38.66					
Ash Z	15.98	32.69	4.32	14.31	16.18	55.12		MR-30	molasses	FeSO ₄	7
Wt Z	71.25	28.75	73.85	16.15	64.57	35.43					
Ash Z	16.02	35.18	3.56	18.14	14.37	61.03		MR-1	humic acid	FeSO ₄	7
Wt Z	77.61	22.39	81.40	18.60	69.09	30.91					
Ash Z	16.00	34.40	3.94	15.59	14.54	51.13		MR-3	molasses		7
Wt Z	76.62	23.38	81.06	18.94	59.68	40.32					

**DATE
FILMED**
8/25/92