Arthur D Little

DOE/PC/89805--T8

DE92 016122

**CROSS-FLOW,
FILTER-SORBENT
CATALYST FOR
PARTICULATE,
SO₂ AND
NO_x CONTROL**

**Technical Progress
Report:**

Seventh Quarterly

4 Qtr 1991

For

U.S. Department of Energy
Office of Fossil Energy
Pittsburgh Energy
Technology Center
Pittsburgh, PA

January 1992

Work Performed Under
Contract No.
22-89PC89805-06

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

Karen Benedek
Arthur D. Little, Inc.
Cambridge, MA 02140

Maria Flytzani-Stephanopoulos
Massachusetts Institute of Technology
Cambridge, MA 02139

ADL Reference 64303

MASTER

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

Table of Contents

1.0 Summary of Seventh Quarter Test Results	1
2.0 Introduction	2
2.1 Emission Control System Requirements for Small-Scale Combustors	2
2.2 Description of Cross-Flow, Filter-Sorbent-Catalyst Emissions Control Device	3
2.3 Active Filter Regeneration Scheme	9
2.4 Research and Development Activity	9
3.0 Task Description Summary	10
4.0 Background/Goals for Cross-Flow, Filter-Sorbent-Catalyst Development ...	11
5.0 Objectives for Seventh Quarter Activity	15
6.0 Approach	15
6.1 Facility Description	15
6.2 Sorbent-Catalysts Materials Tested	17
7.0 Results	18
7.1 Previously Reported Cu-Al Performance	18
7.1.1 Sulfur Removal Efficiency	18
7.1.2 Sorbent Utilization	18
7.1.3 NO _x Reduction	18
7.1.4 Regeneration of Cu-7Al	21
7.2 Comparison Of Cu-7Al DeNO _x Performance With UOP Supported CuO Catalyst	21
7.3 Effect of Space Velocity on Cu-7Al Sulfation and DeNO _x Performance	21
7.4 Previously Reported Cu-Ce Performance	24
7.4.1 Sulfation and NO _x Reduction at 500°C	24
7.4.2 Sulfation and NO _x Reduction at 400°C	24
7.5 Multi-Cycle Performance of Cu-Ce Sorbent/Catalyst	24
7.6 Regeneration	30
7.6.1 Regeneration of Cu-Ce	30
7.6.2 Reduction of SO ₂ over Ceria	30
7.7 Selection of Sorbent Catalyst Material for Monolith Tests	32
8.0 Plans for Next Quarter	32
8.1 Sorbent Studies	32
8.2 Filter Tests	32
9.0 References	37

List of Figures

Figure No.

1	Schematic of a a Ceramic Cross-Flow Filter-Sorbent Catalyst	4
2	Close-Up of Filter-Sorbent-Catalyst Wall and Gas Flow Scheme	5
3	Honeycomb Ceramic Monolith Particulate Filter Configuration	6
4	Commercially-Available Diesel Particulate Filter (Products of Corning Glass Works)	7
5	Ceramic Monolith with Sorbent/Catalyst Material in Clean-Side Channels - Two Options	8
6	Schematic of Packed-Bed Microreactor System	16
7	Breakthrough Profile for Cu-Al-O Sorbent	19
8	NO _x Reduction on Cu-7Al	20
9	NO _x Reduction on Cu-7Al Compared to Supported CuO (UOP)	22
10	Utilization of Cu-7Al Effect of Space Velocity	23
11	NO _x Reduction on Cu-7Al Effect of Space Velocity	25
12	DeSO _x /DeNO _x on Cu-Ce (B2)	26
13	DeSO _x /DeNO _x on Cu-Ce (B2)	27
14	Cyclic Sulfation on 33 CuO-33CuO ₂ -33Al ₂ O ₃	29
15	Regeneration of Sulfated Cu-Ce (B2)	31
16	Sulfur Recovery Schemes (Single-Stage Regeneration - Sulfur Recovery)	34
17	Sulfur Recovery Schemes (Two-Stage Regeneration - Sulfur Recovery)	35
18	Flow Diagram of Typical Parsons Claus Sulfur-Recovery Plant. Courtesy of the Ralph M. Parsons Company	36

List of Tables

Table No.

1	Summary of Tasks	11
2	Revised Program Schedule and Milestone Plan	12
3	Cross-Flow, Filter-Sorbent-Catalyst Concept	13
4	SO ₂ Reduction by CO to Elemental Sulfur On Ce-5	33

1.0 Summary of Seventh Quarter Test Results

This report describes work performed on a new concept for integrated pollutant control: a cross-flow filter comprised of layered, gas permeable membranes that act as a particle filter, an SO₂ sorbent, and a NO_x reduction catalyst. One critical element of the R&D program is the development of mixed metal oxide materials that serve as combined SO₂ sorbents and NO_x reduction catalysts. In this seventh quarterly progress report, we summarize the performance characteristics of three promising sorbent/catalyst materials tested in powder form.

Performance Goals

Our performance goals for the regenerable sorbent/catalyst materials are:

- Provide greater than 90% removal of SO₂ from the flue gas stream;
- Provide 60 - 90% reduction of NO from the flue gas stream;
- Achieve levels of total sorbent utilization that are 2 to 5 times higher than comparable, commercially available, regenerable sorbents;

Achieving these goals will lead to the development of regenerable flue-gas clean-up systems that are appropriate for small-scale combustors and will also compete with advanced, regenerable, emission control systems on large scale applications.

This Quarter's Results

- A ternary mixed-metal oxide material, Cu-Ce-Al, prepared with a co-precipitation method, achieved 100% SO₂ removal efficiency and stable multi-cycle performance. Overall sorbent utilization was 27%, a level that exceeds current state-of-the-art for supported metal oxide sorbents by 2 to 5 times.
- The binary mixed-metal oxide material, Cu-Ce, could not be prepared to achieve stable, multi-cycle performance. The excellent first cycle performance of this material indicates its potential for high sulfur removal efficiency and high utilization, but the material structure degrades during or after regeneration. It was clear that copper-oxide/ceria compounds need some inert material, such as alumina, in the sorbent to provide structural stability throughout the sulfation/regeneration cycle.
- Tests on the regeneration of Cu-Ce revealed the production of elemental sulfur in the regeneration step. These regeneration tests led to a discovery of a very promising single step SO₂ reduction process. This SO₂ conversion process is described below.
- The emission control performance of the binary copper-oxide/alumina material Cu-7Al showed little sensitivity to space velocity, up to values of 10,000hr⁻¹. This is a good result because it implies that the emission control system design will not be limited by a requirement for low space velocities.
- The deNO_x performance of Cu-7Al exceeded that of a commercially available, supported copper-oxide catalyst.

- We have identified a single step, catalytic process to reduce SO_2 directly to elemental sulfur. This is a very significant advance that could be applied to all regenerable sorbent systems that produce concentrated SO_2 offgas streams, as well as to metal smelter technologies. The identification of a single-step, catalytic SO_2 reduction process could lead to the development of a simple, reduced cost, treatment method for concentrated SO_2 streams that would replace the expensive and complex modified Claus Plant.

These studies conclude our work to investigate the performance of bulk mixed-metal oxide sorbent/catalyst materials in powder form. Our next quarter's activity will involve preparations for combined emission control tests in an active ceramic monolith.

2.0 Introduction

2.1 Emission Control System Requirements for Small-Scale Combustors

Emission control systems for small-scale combustors must be designed to provide highly effective removal of three criteria pollutants (particulate matter, SO_2 and NO_x) under a set of operational constraints that are unique to the small-scale application. In residential homes, commercial buildings, and light industrial facilities, the availability of space is limited and there may be no trained, on-site technicians. In this environment, any piece of installed equipment must be safe, reliable, quiet, small, easy to access and maintain, and should produce no waste by-products that cannot be handled by local waste handling systems.

In addition to satisfying these operational requirements, the emission control systems must clean the flue gas to emission levels that are comparable to those produced by existing (fuel-oil) combustors. Reduction or elimination of respirable particulates, odors, and acid mists will be critical because the stacks of these combustors will be low and located in densely populated areas. The deposition of acid-coated particulates will be particularly noticeable in residential areas because these acid smuts eat away the paint on cars and houses.

For high reliability, safety, compactness and cost effectiveness, the emission control system should have few moving parts, involve a minimum of extra flows or treatment process, have high area to volume ratios and produce no additional waste products. It would be desirable to have particulate matter, SO_2 and NO_x controlled by one device that could be easily serviced on a monthly, quarterly or seasonal basis.

These requirements make dry, regenerative clean-up processes particularly attractive. This report describes work performed on a new concept for integrated pollutant control: a cross-flow filter comprised of layered, gas permeable membranes that act as a particle filter, an SO_2 sorbent, and a NO_x reduction catalyst. One critical element of the R&D program is the development of mixed-metal oxide materials that serve as combined SO_2 sorbents and NO_x reduction catalysts. In this seventh quarterly progress report, we summarize the performance characteristics of three promising sorbent/catalyst materials tested in powder form.

2.2 Description of Cross-Flow, Filter-Sorbent-Catalyst Emissions Control Device

The device described in this section will simultaneously remove particulates, SO_2 and NO_x from the combustion gases of coal combustors. The device is configured as a cross-flow filter. One possible cross-flow geometry is shown in Figure 1.¹ The gas flows from the inlet passages to orthogonally oriented discharge channels via thin, multilayered porous walls. As shown in Figure 1, flue gas enters from both the front and back of the device. With the left wall of the filter sealed, gas discharges from the right side of the device. The key to combined physical (fly ash) and chemical (SO_2/NO_x) cleaning is to utilize chemically active sorbent-catalysts (e.g., metal oxides) in the layered walls of the filter. A cross-flow filter wall with layered construction is shown in Figure 2. (This concept is currently under evaluation at MIT; a patent application has been filed.)² This arrangement avoids use of pellet beds that plug in the presence of soot and fly ash and require large reactor volumes because of low surface/volume ratios.

The top (tight-pore) layer serves as a barrier filter blocking passage of fly ash particles. As the gas flows through the porous walls, particulate impurities are trapped on the walls of the inlet passage. The layer is fabricated out of an active sorbent-catalyst material that can absorb and chemically bind SO_2 into the porous wall. The metal oxide sorbent is also a NO_x reduction catalyst before and after it is bound with sulfur-oxides (e.g., CuO and CuSO_4). Thus, with the addition of NH_3 into the flue gas stream, the sorbent layer also serves as a NO_x reduction catalyst.

An alternative cross-flow filter geometry is shown in Figure 3.³ This is the Corning 'honeycomb' monolith design, in which the gas flows in and out of the cross-flow filter along the same axis. The monoliths are extruded in a variety of configurations, sizes and cell densities (Figure 4). A typical material used in the fabrication of these monoliths is cordierite. The open ended monolith is modified by plugging the entrance of every other cell, on each side of the monolith. The alternate cell plugging limits the entrance of the flue gases into every other channel, and subsequently blocks the exit of the flue gases through the channel it entered. The flue gases are then forced to cross through the cell walls and exit through a parallel channel. Ceramem Corporation has developed a process to 'slip' coat these filters to greatly increase the filtration efficiency of the monoliths. To make this particle filter an 'active' filter for SO_2 and NO_x removal, the active sorbent/catalyst material could be coated in the 'clean' cells, or it could be filled in these clean-side cells like a porous sponge, as shown in Figure 5.

Another variant on the combined emission control device includes the separation of the particle removal function and the combined $\text{deSO}_2/\text{deNO}_x$ function. In this design, a small percentage of the cross-flow filters would be used for particle filtration upstream of the active ($\text{deSO}_2/\text{deNO}_x$) filters. In some applications, this separated system may be more economical than a three pollutant cross-flow filter.

All the configurations described above offer a compact filter (10 to 100 times higher surface-to-volume ratio than a typical baghouse), a low-attrition sorbent-catalyst (no moving or fluidized solid bed), low pressure drop (through a few mm-thick macroporous membrane), and a very simple flow scheme.

Figure 1. Schematic of a Ceramic Cross-Flow Filter-Sorbent Catalyst

Figure 2. Close-up of Filter-Sorbent-Catalyst Wall and Gas Flow Scheme

Figure 3. Honeycomb Ceramic Monolith Particulate Filter Configuration

Figure 4. Commercially Available Diesel Particulate Filters (Products of Corning Glass Works)

Figure 5. Ceramic Monolith with Sorbent/Catalyst Material in Clean-Side Channels - Two Options

We estimate that better than 90% removal efficiency of SO_2 and 60 - 90% removal of NO_x is achievable with the use of mixed metal oxide sorbent/catalysts (CuO , CeO_2) in the device. High sulfur capacity, as well as high sulfur removal efficiency, is also desirable in this device so that regeneration intervals can be sufficiently long for economic operation of the system. Maximizing sulfur capacity through sorbent/catalyst material improvements and design innovations is one important goal of this R&D program. Sulfur capacity can be increased in three ways: by increasing the active metal oxide content of the SO_2 sorbent (which typically contains some amount of inert material for structural reasons); by increasing the utilization of the active material in the sorbent; and by increasing the mass of sorbent material layered in the cross-flow filter device.

Aluminum oxide Al_2O_3 , will be used as a dispersant and/or catalyst support in the active sorbent-catalyst layer(s). The composite is expected to keep its bifunctional characteristics throughout its operation and not deactivate or lose its structural integrity in the presence of temperature cycles, fly ash, and/or trace metals. As was indicated above, however, the amount of Al_2O_3 used needs to be kept to a minimum in order to achieve high sulfur capacity with these sorbents.

2.3 Active Filter Regeneration Scheme

Fly ash particles trapped by the cross flow structure can be periodically removed by a back-flushing procedure. Pulse-jet backflushing is a well established technique for high pressure applications of the cross-flow filter.¹ This technique is modified somewhat for small-scale applications. Modifications include: frequency of backflush, duration and pressure of each pulse, and pressure source for the pulsation. The modifications are necessary to make the system as simple as possible for small-scale use.

The SO_2 sorbent can be renewed by a regeneration procedure that produces either elemental sulfur or concentrated gaseous sulfur species which can be converted to elemental sulfur by well established processes. We have also identified and conducted preliminary tests on a one-step process to reduce the concentrated SO_2 offgas stream to elemental sulfur. This one-step sulfur reduction technique will greatly improve the economics of a wide variety of regenerable sorbent systems.

The single unit, particle filter, SO_2 sorbent, NO_x reduction catalyst is an ideal device for small-scale applications. It is modular in configuration, compact, quiet; it has no moving parts, produces no toxic materials or new solid wastes to be disposed of and requires little auxiliary power.

2.4 Research and Development Activity

In October 1989, the team of Arthur D. Little, Massachusetts Institute of Technology, and GTE began a thirty month, USDOE/PETC (Pittsburgh Energy Technology Center) funded program to research and develop the filter-sorbent-catalyst. The research priorities of this effort are listed below:

- Sorbent-catalyst material development
 - Which metal oxide materials provide best combined performance for SO₂ removal, NO_x reduction, sulfur capacity and sorbent regeneration?
 - Under what regeneration conditions is the production of elemental sulfur maximized?
- Active filter selection
 - What ceramic filter design (thickness, porosity, size, active-phase layering) leads to acceptable pressure drop, particulate matter capture, and structural integrity at expected operating conditions?
 - What backflushing scheme is required?
- System design
 - How will these systems be incorporated into combustion systems?
 - What will be the device size, configuration, cost, and operating constraints?
 - How does the system compare in cost and performance to other systems on the market or under development?

3.0 Task Description Summary

The objective of this program is to successfully carry out the experiment and design tasks described herein that will lead to the development a cross flow filter-sorbent-catalyst. We have carried out this research and design work in two stages.

The first stage of the work has been fundamental in nature: we have investigated the SO₂ removal and NO_x reduction characteristics of different sorbent-catalyst compositions (in bulk, granular form), and we have conducted exploratory tests of cross-flow filters under conditions similar to those found in the combustion gases of small-scale combustors. After these fundamental studies, we conducted a preliminary evaluation of the component performance and designed a set of prototype configurations.

In the subsequent stage of the program, we will investigate the pollutant control characteristics of prototype filter-sorbent-catalyst devices. The SO₂ removal and NO_x reduction efficiency of a 'unit-element' prototype will be investigated. This 'unit element' will be a ceramic honeycomb monolith coated, or otherwise layered, with filter-sorbent-catalyst material. The particulate collection efficiency and back-flushing requirements of an active, (ie sorbent filled) monolith will be tested.

Concurrent with these efforts will be the investigation of a sorbent regeneration scheme that has the potential to produce elemental sulfur in a one step process. Final evaluation

of component performance and the design of these emissions control devices for residential, commercial, and small industrial applications will be conducted at the conclusion of the project.

Table 1 summarizes the program tasks. A milestone chart is shown in Table 2. A complete description of each task can be found in First Quarterly Technical Progress Report (March, 1990).⁴

Table 1. Summary of Tasks

Task #	Description	Lead Contractor	Schedules
1	Test Plan	ADL	Oct. 1989 - Dec. 1989
2	Component Development		
	2.1 Preparation for SO ₂ /NO _x Studies	MIT	Oct. 1989 - Oct. 1990
	2.2 SO ₂ /NO _x Screening Tests	MIT	Oct. 1989 - Aug. 1991
	2.3 Particulate Tests	ADL	Jan. 1990 - Aug. 1991
	2.4 Regeneration Studies	MIT	Aug. 1990 - Aug. 1991
3	Prototype Tests		
	3.1 Filter Fabrication	GTE	Apr. 1991 - July 1991
	3.2 SO ₂ /NO _x Tests	MIT	Sept. 1991 - Jan. 1992
	3.3 Particulate Tests	ADL	Nov. 1991 - Feb. 1992
4	Evaluation and Design	ADL	Feb 1991 - July 1991 and Oct. 1991 - Feb. 1992
5	Management and Reports	ADL	Oct. 1989 - Feb. 1992

4.0 Background/Goals for Cross-Flow, Filter-Sorbent-Catalyst Development

The cross-flow, filter-sorbent-catalyst technology is based on a number of independent filter and sorbent technologies that have been under development for a variety of different applications. A summary of the background for the technology and the innovations that will be explored in this program is presented in Table 3 and discussed below.

Cross-Flow Filter For Particle Removal - Background

Ceramic, cross-flow filters for particle removal under conditions of high temperature and high pressure have been under development for many years. Westinghouse patented the cross-flow filter configuration shown in Figure 1¹ and has been developing it to filter gases upstream of the gas turbine for pressurized fluidized bed and coal gasifier applications. Manufacturers of this style of cross-flow filter include GTE and Coors Porcelain Company. A backflushing scheme that is suited for high pressure applications has been established by Westinghouse engineers.

Table 2. Revised Program Schedule and Milestone Plan

Table 3. Cross-Flow, Filter-Sorbent-Catalyst Concept

Component	Concept Background	Innovation
Cross-Flow Filter	High pressure/temp use for PFBC/gasifier	Lower temp, pressure Lower ΔP requirement
CuO, CeO ₂ as SO ₂ Sorbents	CuO, CeO ₂ supported on Al ₂ O ₃ Sulfation at: 400°C, 600°C Regenerate with CH ₄ , H ₂	<ul style="list-style-type: none"> • Bulk sorbents • Mixed metal oxides • Higher capacity • Regenerate with CO to produce S
CuO, CeO ₂ as SCR Catalysts	Good NO _x reduction with sulfated CuO	Optimize system for combined SO ₂ removal and NO _x reduction
Integrated System	No previous experience	Compact Effective Small scale

A cross-flow filter system for flue gas particle removal (based on a honeycomb monolith filter design) has been developed and tested by Ceramem Corporation. Ceramem has tested successfully their coated, cross-flow, ceramic monolith filters in a flue gas slip-stream of a utility boiler. The filtration efficiency, backflushing effectiveness and pressure drop history for these filters in a utility application are being established.

Cross-Flow Filter Development - Innovations

We plan to test cross-flow filters under conditions and constraints typical of small-scale combustors. In this application, allowable pressure drop is lower than for PFBC, IGCC or even utility flue gas clean-up applications. We need to establish backflushing guidelines to maintain overall pressure drop for the combined combustion and flue gas clean-up system at less than 4 inches of water. We are also working with fly ash that will contain a higher carbon content than the previously tested systems. Most importantly, we will be testing a cross-flow filter that is coated with sorbent material. We need to establish the maximum thickness of sorbent material that can be coated on the filter and still provide acceptable pressure drop and backflushing characteristics.

Regenerable Sorbent-Catalyst Materials - Background

The Department of Energy, Pittsburgh Energy Technology Center has been developing regenerable, metal oxide, sorbent-catalysts with projected SO_2 and NO_x pollutant removal efficiencies of 80 - 90%. The sorbent-catalysts being developed are supported, single metal oxides, such as copper oxide, or ceria. These sorbents are generally coated alumina pellets. The coating of the pellet constitutes roughly 5 - 10% of the overall pellet mass. The flue gas contacts the sorbent coated pellets in a fluidized or moving bed reactor. This system has been shown to provide high pollutant removal efficiency⁵, but the active material rapidly wears-off of the pellet in the fluidized or moving bed geometry. This active layer attrition results in a high maintenance cost for the system. Another characteristic of this technology that leads to high cost is the low concentration of active material on each pellet. The low concentration (less than 10% loading in most cases) requires the use of large amounts of pellets, and therefore large reactors; the large reactor size leads to high system cost.

Regeneration of the copper oxide sorbent is achieved with methane, hydrogen or coal gas. A stream of high concentration sulfur dioxide results from the regeneration step. It is planned that this SO_2 stream will be processed in a modified Claus reactor to produce elemental sulfur.

Regenerable Sorbent-Catalyst Development - Innovations

We are developing bulk sorbent materials as an alternative to supported sorbent materials. The bulk sorbents can contain up to 100% active material, compared to the supported material which can contain up to 10% active material. However, because of structural requirements (strength, friability) the bulk sorbents will probably contain some inactive material (e.g., alumina). Our goal is to achieve overall sorbent utilization of greater than 25%. This will result in a 2 to 5 fold improvement of over current technology. The increase in sorbent utilization can be directly related to capital cost.

We also are developing a sorbent configuration that is a fixed bed instead of a fluidized bed or moving bed. The fixed bed configuration virtually eliminates sorbent attrition and the maintenance cost associated with sorbent replacement.

We are developing mixed metal oxide sorbent-catalysts, as opposed to single oxide sorbent-catalysts. The combination of ceria, copper oxide and alumina can result in improved optimization of combined SO_2 and NO_x removal. For example, small amounts of ceria can improve the deNO_x capability of the sorbents, while the copper provides the majority of the SO_2 removal.

Finally, we are researching new sorbent regeneration chemistry. By using CO as a reducing gas (instead of methane or hydrogen) we can take advantage of materials that exhibit selectivity for the production of elemental sulfur in the regeneration process. The elimination, or even simplification, of regeneration off-gas treatment facilities would provide a significant cost reduction for regenerable sorbent technologies.

5.0 Objectives for Seventh Quarter Activity

The objective of the seventh quarter's activity was to complete the testing of sorbent/catalyst powders (Task 2.2) and to select a material to be used in the monolith tests (Task 3.2). This quarter's tests included:

- Investigation of multi-cycle performance of Cu-Ce sorbent at 500°C . (Single cycle performance of this material was investigated last quarter and was found to be very promising);
- Comparison of the deNO_x performance of our bulk copper-alumina sorbent/catalysts with the performance of a commercially available, supported copper oxide sorbent/catalyst (manufactured by UOP).
- Investigation of the effect of space velocity on bulk sorbent/catalyst deNO_x and deSO_x performance; and
- Examination of the regeneration chemistry of various mixed-metal oxide materials.

6.0 Approach

6.1 Facility Description

The microreactor test facility used for combined SO_2 removal and NO_x reduction tests and sorbent regeneration studies is shown schematically in Figure 6.

The reactor consists of a quartz tube of 1.5 cm I.D. vertically mounted inside an electric furnace equipped with a temperature controller. The sorbent-catalyst granules are supported on a fritted quartz disc in the middle in the reactor tube. The total volume of sorbent/catalyst tested in the microreactor is 5 to 8 cubic centimeters. This volume corresponds to roughly 0.5 to 1 gram, depending on the material composition and preparation method used. A K-type thermocouple moving inside a quartz thermowell (0.3 cm I.D.) concentric to the reactor is used to monitor the axial bed temperature. The

Figure 6. Schematic of Packed-Bed Microreactor System

reactor pressure is slightly above atmospheric. Premixed gas streams of typical flue gas compositions flow through the reactor in the upward (sulfation- NO_x reduction) or downward (regeneration) direction.

Product gases are analyzed for SO_2 (during sulfation) and SO_2 and other sulfur compounds (e.g., COS, CS_2 (during regeneration)) by a Hewlett-Packard 5880A gas chromatograph equipped with flame photometric and thermal conductivity detectors. A chemiluminescent NO_x analyzer is used to monitor nitrogen species.

In combined SO_2/NO_x removal tests, the feed gas contains 1500 ppm SO_2 , 600 ppm NO, 600 ppm NH_3 , 3% O_2 and N_2 balance. The gas flow rate corresponds to a space velocity of $2,000 \text{ hr}^{-1}$. With the present chemiluminescent NO_x analyzer, the concentration of NO component and ($\text{NO}_x + \text{NH}_3$) mixture can be determined precisely. However, no direct information about concentrations of other single nitrogen oxides (except NO) is available. The conversion of NO can be obtained by monitoring the NO concentration change in the flue gas flow passing through the reactor tube. In addition, selectivities and conversions of NO reduction by ammonia can be reconfirmed by monitoring the concentration change of the ($\text{NO}_x + \text{NH}_3$) mixture.

6.2 Sorbent-Catalysts Materials Tested

In this quarter we focused our investigations on the two most promising materials investigated thus far in this program:

- Cu-Ce, an equimolar mix of copper oxide and ceria, and
 - Cu-7Al, a 7:1 molar mixture of copper-oxide and alumina.
- Both of these dry, regenerable sorbents are bulk materials as opposed to sorbents supported on an inert material such as alumina.

Except where noted, the sorbent/catalyst materials are prepared according to the amorphous citrate technique.^{6,7} This involves rapid dehydration (under vacuum, at 70°C) of an aqueous solution containing the metal salts and citric acid in desired proportions, followed by pyrolysis and further calcination of the resulting amorphous solid foam at relatively low temperatures ($500 - 600^\circ\text{C}$). Citric acid is added in a 1 to 1 mole ratio to the metal salts included in the solution. Homogeneous, highly dispersed mixed oxides or oxide solid solutions are formed. For the tests in the microreactor, the foam is ground and separated into particles sized between 20 and 35 mesh (400 - 800 microns).

The single cycle performance of Cu-Ce was tested in the spring of 1991 and was reported in the fifth quarterly report (May 1991)⁸. The performance of bulk Cu-7Al, our baseline material, was investigated over a year ago and was reported in the second quarterly report (May 1990)⁹. In this quarter we investigated the multicycle performance of the Cu-Ce and we conducted some additional tests with the Cu-7Al sorbent to investigate the importance of space velocity on sulfation and deNO_x performance, and to compare the Cu-7Al performance with commercially available sorbent materials. Last quarter we selected these materials as candidates for testing in layered form.

The results of earlier tests on these two sorbent/catalyst materials are summarized below with the results of the work conducted this quarter.

7.0 Results

7.1 Previously Reported Cu-Al Performance

7.1.1 Sulfur Removal Efficiency

The performance of bulk Cu-7Al, our baseline material, was investigated over a year ago. The sulfur removal efficiency of this sorbent is high: 100% prior to 'breakthrough', when the sorbent is fully sulfated, and SO₂ in the inlet gas stream passes, unreacted, through the sorbent. At breakthrough, the utilization of the copper in the sorbent is close to 100%. This means that almost all of the copper, or active material, in the sorbent is being sulfated. The bulk Cu-7Al material has a surface area of 373 m²/g and a pore volume of 1.6 g/cc. Analysis of the sorbent by XRD shows that its structure is amorphous.

Figure 7 shows SO₂ breakthrough profiles for four Cu-7Al cycles. These sulfation tests were conducted at 400°C. The plot shows the SO₂ emission rate out of the sorbent as a function of normalized time, t/t^* . The parameter t^* is defined as the time required for all the active material in the sorbent sample to be completely sulfated. This parameter, t^* , is a theoretical, calculated value based as the mass of sorbent tested, the flow rate of SO₂ into the sorbent and an assumed stoichiometry for the sorbent sulfation reaction.

Figure 7 shows that:

- prior to breakthrough, the SO₂ emission rate from the sorbent is 0 ppm - i.e., sulfur removal efficiency is 100% prior breakthrough;
- after repeated cycles of testing, the value of t/t^* prior to breakthrough is close to 1. This means that almost all the copper in the sorbent is being sulfated.

7.1.2 Sorbent Utilization

The utilization of the copper in the Cu-7Al sorbent is high because the copper is well dispersed in the Al₂O₃. The grains of CuO are small and readily accessible to the SO₂ gas passing through the sorbent. Though the copper utilization is high, the overall sorbent utilization (CuO and Al₂O₃) is only 18% because the sorbent contains 82% inert material (Al₂O₃). This overall sorbent utilization is roughly 2 to 3 times higher than commercially available supported CuO where in the total material utilization is 5 to 10%. Of course, the final calculation of sorbent utilization for our bulk materials must consider the cross-flow filter structure as well. The ratio of inert material in the cross-flow filter to active material in the channels will depend on filter fabrication methods, cost, and pressure drop considerations.

7.1.3 NO_x Reduction

Figure 8 shows NO_x reduction on Cu-7Al as a function of reaction temperature for fresh and partially sulfated materials. All these tests were conducted with an NO-NH₃-N₂ gas

Figure 7. Breakthrough Profile for Cu-Al-O Sorbent

Figure 8 NOx Reduction on Cu-7Al

600 ppm NO, 600 ppm NH3
3% O2, Balance N2, SV: 2,000 hr-1

mixture. The results show that NO_x reduction at 400°C over fresh Cu-7Al was 55%, over partially (20%) sulfated Cu-7Al was 80%, and over partially (30%) sulfated Cu-7Al was 100%.

We observed a significant improvement in NO_x reduction when SO_2 is present in the gas stream. Over fresh sorbent, at 400°C , deNO_x improved from 55% to 90% over a period of 30 minutes. Under the conditions of these tests, 30 minutes of testing results in less than 10% sulfation of the sorbent. This indicates that the beneficial effects of sulfated sorbent for NO_x reduction can be obtained at very low sulfation levels. The presence of sulfates apparently suppresses the ammonia oxidation reaction.

7.1.4 Regeneration of Cu-7Al

Regeneration of copper-alumina sorbents can be conducted at 400°C with 10% CO and nitrogen balance. The bulk of SO_2 regeneration occurs at 400°C , though smaller peaks of SO_2 do occur at 450 and 500°C . During regeneration of Cu-Al compounds, only SO_2 is formed. The temperature of regeneration can be used to control the degree of residual sulfur that is left in the sorbent. Small amounts of residual sulfur may be useful to enhance NO_x reduction at the start of a new sulfation cycle.

7.2 Comparison Of Cu-7Al deNO_x Performance With UOP Supported CuO Catalyst

The NO_x reduction performance of a UOP prepared copper oxide supported catalyst was tested and compared to the deNO_x performance of the bulk Cu-7Al catalyst. The tests were conducted on a fully sulfated UOP catalyst. This catalyst contained 5 - 6% copper oxide on an alumina pellet substrate. The deNO_x tests were conducted with 600 ppm NO and 600 ppm NH_3 with 3% O_2 at a space velocity of 2000 hr^{-1} . The results are plotted in Figure 9. The highest NO_x reduction efficiency was about 80% at 350°C . NO_x reduction performance fell to less than 50% efficiency at temperatures of 100°C above and below this optimum temperature.

As is shown in the same figure, the NO_x reduction performance of the bulk, partially sulfated, Cu-7Al was superior to the supported, fully sulfated, CuO catalyst at almost all temperatures. The NO_x reduction tests for the Cu-7Al were conducted at identical conditions to the UOP catalyst.

7.3 Effect of Space Velocity on Cu-7Al Sulfation and deNO_x Performance

Sulfation and NO_x reduction tests for all sorbents had been conducted at 2000 hr^{-1} . We conducted some limited additional tests to assess the effect of space velocity on both sulfation and NO_x reduction performance. The advantage of operation at higher space velocities is the ability to reduce reactor size and therefore decrease capital cost. We examined sulfation and deNO_x performance at $10,000 \text{ hr}^{-1}$, a five fold increase in space velocity.

We found that space velocity had no effect on sulfation performance, as is shown in Figure 10. Similarly, NO_x reduction performance at temperatures between 350°C and 500°C showed little effect of space velocity. However, the low temperature NO_x

Figure 9 NOx Reduction on Cu-7Al
Compared to Supported CuO (UOP)

600 ppm NO, 600 ppm NH3
3% O2, Balance N2, SV: 2000hr-1

Figure 10 Utilization of Cu-7Al
Effect of Space Velocity

Cu-7Al (B2), T_{regen}: 400C

reduction performance of the Cu-7Al changed with increased space velocity. Below 350°C, the NO_x reduction efficiency decreased rapidly with decreasing temperature at the higher space velocity. We had found very high conversion of NO at low temperature at lower space velocities. These results are shown in Figure 11. We plan to investigate the low temperature NO_x reduction performance of this sorbent/catalyst in more detail in the monolith tests.

7.4 Previously Reported Cu-Ce Performance

This bulk binary sorbent contains no inert materials. The copper and cerium are added in a molar ratio of 1:1 which corresponds to a mass distribution of 32% CuO and 68% CeO₂. The performance of the Cu-Ce(B2) sorbent (B2 indicating the second preparation method used) was investigated at two temperatures, 400°C and 500°C. In these tests SO₂ removal and NO_x reduction experiments were conducted simultaneously. The first cycle performance of this sorbent/catalyst at each temperature is discussed below.

7.4.1 Sulfation and NO_x Reduction at 500°C

Figure 12 shows the SO₂ removal and NO_x reduction performance of Cu-Ce(B2) at 500°C. The first cycle performance shows that SO₂ removal efficiency is 100% until the sorbent is fully sulfated. In the first sulfation cycle, 100% utilization of the sorbent is achieved. These preliminary results exceeded our performance goals for the sorbent.

At 500°C, the steady state NO_x conversion is 68%. The first data point taken, corresponding to fresh sorbent, shows a NO_x conversion of 21%, but this conversion efficiency rapidly increases to 50% after 2-5% sulfation of the sorbent. The NO_x reduction efficiency gradually increases from 50% to 68% as the sorbent becomes more sulfated. A steady state NO_x reduction efficiency of 68% is reached when the sorbent is 50% sulfated.

7.4.2 Sulfation and NO_x Reduction at 400°C

At 400°C, NO_x reduction efficiency over Cu-Ce(B2) is much higher than at 500°C, but the sulfur capacity of the sorbent is lower. These data are shown in Figure 13. The SO₂ removal efficiency of Cu-Ce(B2) at 400°C is still 100% prior to breakthrough, but breakthrough occurs after 30% of the total available sorbent material is sulfated. At 400°C, almost all of the copper is sulfating, but the copper is only 32% weight of the sorbent. Apparently the temperature is too low for any cerium sulfation to be observed.

The NO_x reduction performance at 400°C is very good. The steady state NO_x conversion is 90%. NO_x reduction over fresh sorbent is 80%, but this performance quickly rises to 90% after less than 5% of the sorbent material is sulfated.

7.5 Multi-Cycle Performance of Cu-Ce Sorbent/Catalyst

We examined the multi-cycle performance of the Cu-Ce sorbent sulfated at 500°C. As described above, we found that this sorbent had excellent first cycle performance (100% utilization of sorbent). This quarter we examined how the sorbent behaved after

Figure 11 NO_x Reduction on Cu-7Al
Effect of Space Velocity

600 ppm NO, 600 ppm NH₃
3% O₂, Balance N₂, SV: as noted

Figure 12. DeSO₂/DeNO_x on Cu-Ce (B2)

Figure 13. DeSO_x/DeNO_x on Cu-Ce(B2)

regeneration. We found that the second cycle performance of the Cu-Ce sorbent was degraded as compared to the first cycle performance. Cu-Ce utilization dropped from 100% in the first cycle to 65% in the second cycle.

We hypothesize that the Cu-Ce material suffers structural degradation after or during regeneration at 600°C. (Regeneration at this temperature is necessary to drive the SO₂ out of the ceria.) A number of new sorbent preparation techniques and/or sulfation conditions were explored to reduce or eliminate this sorbent degradation problem:

We calcined the Cu-Ce at 800°C (instead of the standard 500°C) in an attempt to make the structure 'immune' to degradation at 600°C during regeneration, but this sorbent did not have good first or second cycle performance (36% and 20% sorbent utilization, respectively).

We sulfated a new preparation of Cu-Ce at 450°C, instead of 500°C, with the thought that the material would be easier to regenerate if it had not been fully sulfated prior to regeneration. Unfortunately, regeneration at 600°C still resulted in significant decrease in sulfur capacity during the subsequent sulfation steps. Sulfating at 450°C, the first cycle sorbent utilization was 44%, second cycle utilization was 21% and third cycle utilization was 14%.

We examined Cu-Ce prepared in such a way as to have independent copper oxide particles and ceria particles as a mixture, instead of as a solid solution. The sulfation of the mixture was very high, thus demonstrating that the mixture of the oxides is as effective in sulfation as a solid solution of the two oxides. This test of material structure is important because it opens the possibility of alternative preparation techniques to the citric acid technique currently being used to make the sorbents. Unfortunately, we found that even the mixture of particles suffered degradation during regeneration. Apparently, the atomic structure of the material is rearranged during regeneration to the extent that SO₂ does not have access to sites for sulfation.

The tests described above have indicated that the binary Cu-Ce sorbent is not structurally stable enough to be used alone as a sorbent material. Some additional structural material in the sorbent will be necessary to hold pores open through the cyclic sulfation/regeneration process.

We explored the possibility of using alumina to provide structural stability to the Cu-Ce sorbent by preparing a Cu-Ce-Al sorbent using a co-precipitation method. (We found in earlier work that a stable, effective, Cu-Ce-Al ternary sorbent could not be prepared according to the standard amorphous citrate technique.)⁹ In the coprecipitation method, salts of copper, cerium and aluminum are combined with sodium carbonate in water. The carbonate precipitates the metals; sodium is washed out of the precipitate. The mixture is fired at 550°C to produce metal oxides.

The sulfation performance of the Cu-Ce-Al mixture (33% each by mass) is shown in Figure 14. The material was sulfated at 500°C and regenerated at 600°C. We found that the multicycle performance of this sorbent stabilizes at about 40% utilization of the active material. This corresponds to an overall sorbent utilization of 27%.

Figure 14. Cyclic Sulfation of 33 CuO-33CuO₂-33A1203

This work demonstrates the importance of preparation method on sorbent stability and utilization. It opens a window to additional work to examine improved performance of ternary sorbents prepared by a coprecipitation method. Though this work appears potentially promising, additional study of these sorbents is beyond the scope of our current program.

7.6 Regeneration

7.6.1 Regeneration of Cu-Ce

The multi-cycle sulfation results of the Cu-Ce sorbent have shown that it is not stable enough to be considered a promising sorbent/catalyst material. However, we are still interested in studying its regeneration performance because of the selectivity of ceria for elemental sulfur during regeneration. Results obtained in the study of Cu-Ce will be applicable to more promising ternary sorbents.

Figure 15 shows the regeneration performance of sulfated Cu-Ce(B2). The material investigated here was sulfated at 500°C. Under these conditions, both copper and ceria were sulfated completely prior to regeneration. Regeneration was performed with 10% CO, 10% CO₂, balance N₂. The Figure 15 shows regeneration products at temperatures ranging from 500 to 600°C. Key features of Cu-Ce(B2) regeneration are as follows:

- Cu-Ce(B2) (sulfated at 500°C) needs to be regenerated at 600°C or higher.
- At 600°C, three products of regeneration were observed: SO₂, COS and S. The sulfur was collected in an ice bath and is not indicated in the figure.
- The regeneration rates are rapid and the regeneration gas concentration falls to zero rapidly; there is little production of tail gases that create problems for downstream treatment.

As was indicated above, the regeneration conditions required to reduce the sorbent to its original state are harsh enough to cause significant structural degradation of the sorbent material itself. This structural degradation leads to reduced sulfation performance in the second cycle. These problems of degradation during regeneration do not exist for Cu-Al sorbents because they are regenerated at 400 - 500°C, instead of at 600°C. The lower temperature regeneration, combined with the inert alumina framework, maintains a stable material structure throughout the cycles of sulfation and regeneration.

7.6.2 Reduction of SO₂ over Ceria

The selectivity of ceria for the production of sulfur during regeneration lead us to investigate the potential for using ceria as a catalyst to reduce sulfur dioxide (with carbon monoxide). The reduction reaction was carried out using various concentrations of CO, 10% CO₂ and nitrogen balance. We examined process streams with CO/SO₂ concentration ratios of around 2, because this ratio is stoichiometrically required for the complete reduction of SO₂ to elemental sulfur. Higher CO/SO₂ ratios will favor the production of COS.

Figure 15. Regeneration of Sulfated Cu-Ce(B2)

The very promising results of these tests are shown in Table 4. These data show that SO_2 can indeed be reduced to elemental sulfur very efficiently in a single step process, with some recycling of the outlet stream. The results show that single step reduction of SO_2 can range in efficiency from 80% to 100% as the CO/SO_2 ratio is increased from 1.6 to 2.3. The percentage of elemental sulfur produced from the reduction of the SO_2 ranges from 98% to 67% as the CO/SO_2 ratio is varied in this same range. The data show a trade-off between overall conversion of SO_2 (to sulfur and other reduced species, such as COS) and the percentage of elemental sulfur in the reduced gas stream. The higher the CO/SO_2 ratio in the gas, the higher the overall conversion of SO_2 to reduced forms. But as overall conversion increases, the concentration of sulfur in the reduced gas stream decreases.

These results show that a potentially simple process exists for treating the waste streams from a wide range of SO_2 producing processes, such as the regeneration gases from sulfur sorbents and metal smelter offgases. (A patent application for elemental sulfur recovery process has been filed.¹¹) The reaction documented above would be a significant improvement over a modified Claus plant process which includes dozens of process steps to reduce SO_2 to elemental sulfur.

We plan to investigate process options for this catalytic reaction in more detail as part of our Phase II Evaluation and Design task. Preliminary concepts for the integration of this reaction in a SO_2 offgas treatment process are shown in Figures 16 and 17. These process schematics show a very simple once through or recycle process for SO_2 treatment. A schematic of a modified Claus plant, frequently cited as a potential treatment method for regeneration offgas streams¹⁰, is shown in Figure 18 for comparison. It is obvious that potential exists for a simplified treatment process for all SO_2 rich offgas streams.

7.7 Selection of Sorbent Catalyst Material for Monolith Tests

We have chosen to proceed to monolith tests with the Cu-7Al sorbent. This material has exhibited excellent SO_2 removal efficiency, high deNO_x activity and good sulfur capacity. The ternary sorbent Cu-Ce-Al looked very promising, and, in fact, showed higher sulfur capacity than the Cu-7Al, but the material would need additional testing in powdered form prior to layer tests. Because of schedule and cost constraints, we have chosen to proceed with the material that we have identified throughout the program as our 'baseline' material.

8.0 Plans for Next Quarter

8.1 Sorbent Studies

We will prepare the facility for testing sorbents in layered form and will begin tests of the active monolith filters

8.2 Filter Tests

We will prepare the facility for testing the particle removal efficiency and pressure drop characteristics of active monolith filters.

Table 4. SO₂ Reduction by CO to Elemental Sulfur on Ce-5

Gas Composition: x% CO-1.3% SO₂-5% CO₂-N₂ Balance

Reaction Temperature: 773K

CO/SO ₂ Ratio	SO ₂ Conversion (%)	Selectivity (%)	
		S	COS
1.63	80.5	97.8	2.2
1.90	91.5	95.2	4.8
2.33	100	67.0	33.0

(A) Single-Stage Regeneration - Sulfur Recovery

* Sulfated Cu-Ce

Figure 16. Sulfur Recovery Schemes (Single-Stage Regeneration - Sulfur Recovery)

(B) Two-Stage Regeneration - Sulfur Recovery

Figure 17. Sulfur Recovery Schemes (Two-Stage Regeneration - Sulfur Recovery)

Figure 18. Flow Diagram of Typical Parsons Claus Sulfur-Recovery Plant. Courtesy of The Ralph M. Parsons Co.

9.0 References

1. Ciliberti, D.F., Et Al., "Hot Gas Clean-up Using Ceramic Cross Flow Membrane Filters," Final Report under DOE Contr. No. DE-AC21-79ET15491, December 1983.
2. Flytzani-Stephanopoulos, M., "Methods and Devices for Gas Cleaning," U.S. Patent Application - Serial No. 113, 572, filed October 23, 1987.
3. Goldsmith, R. L. and Bishop, B. A., "Ceramic Filter for Removal of Particulates form Flue Gas," presented at the Seventh Annual Coal Preparation, Utilization, And Environmental Control Contactor's Conference, July 15 - 18 1991, Pittsburgh, PA. Contract Number DE-FG02-90ER80897.
4. Benedek, K., Flytzani-Stephanopoulos, M., First Quarterly Technical Progress Report, March 1990, Contract No. 22-89PC-89805-00.
5. U. S. DOE, Pittsburgh Energy Technology Center, Summary of Ongoing Flue Gas Clean-up Programs, 1988.
6. Marcily, C., Courty, P., And Delmon, B., *J. Am. Cer. Soc.* 53 (1), 56 (1970).
7. Courty, P., And Marcilly, C., "A Scientific Approach to the Preparation of Bulk Mixed Oxide Catalysts," in *Preparation of Catalysts III*, ed. by G. Poncelet, P., Grange and P.A. Jacobs, Elsevier, Amsterdam, pp. 485-519, 1983.
8. Benedek, K., Flytzani-Stephanopoulos, M., Fifth Quarterly Technical Progress Report, May 1991, Contract No. 22-89PC-89805-05.
9. Benedek, K., Flytzani-Stephanopoulos, M., Second Quarterly Technical Progress Report, May 1990, Contract No. 22-89PC-89805-00.
10. Grayson, M., Kirk-Othmer Encyclopedia of Chemical Technology, Third Edition, John Wiley & Sons, 1978.
11. Flytzani-Stephanopoulos, M., Elemental Sulfur Recovery Process," U.S. Patent Application Serial No. 07-791,491, filed November, 12 1991.

**DATE
FILMED**

8/27/92