DOE/PC/88856--T5

DE92 016138

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

Quarterly Technical Progress Report No. 5
For Period
February 1 thru April 30, 1989

SURFACE MAGNETIC ENHANCEMENT FOR COAL CLEANING

Submitted to:

U.S. Department of Energy
Pittsburgh Energy Technology Center
P.O. Box 10940
Pittsburgh, PA 15236

Contract Number: DE-AC22-88PC88856**Technical Program Officer: McMahan L. Gray**

Prepared by:

Project Manager
Tom E. Scott
Director

Principal Investigator
J. Y. Hwang
Program Manager - Minerals

Institute of Materials Processing
Michigan Technological University
Houghton, Michigan 49931

MASTER

SUMMARY AND FUTURE WORK

Phase I study, which investigates the fundamental chemistry and properties of magnetizing reagents, is completed in this reporting period. Phase II study is initiated to apply the results of Phase I study for coal cleaning. Coal samples for Phase II work have been selected, ordered, and received. Processing and characterization of coal samples are in progress. Preliminary tests show that significant ash and sulfur reduction can be obtained with the magnetizing reagent method.

The work is slightly behind the schedule due to the delay of coal shipment. Since the coal samples have been received, the schedule will be caught up in the next quarter. The major work for the next quarter will be the processing and characterization of coals and the optimization of magnetizing conditions for each coal.

INTRODUCTION

This research studies the surface enhancement of magnetic susceptibility of minerals for coal cleaning by adsorbing magnetizing reagent on minerals. The objectives of the study include: (i) to define the optimal conditions of adsorption selectivity and magnetic enhancement for magnetizing reagents, (ii) to determine the effect of such magnetic enhancement on the coal cleaning efficiency with magnetic separations, and (iii) to evaluate where this method can be adapted to the existing coal processing schemes for maximum effectiveness.

Three phases of work are included in this research: a fundamental study, an application study, and an industrial laboratory study. The fundamental study investigates the basic chemistry involved in the interactions of magnetizing reagents and minerals. The application study will apply the basic chemistry for coal cleaning under various process schemes. The work performed during this reporting period including the completion of Phase I study and the initiation of Phase II study.

PROGRESS BY WORK BREAKDOWN STRUCTURE

Task 1. Magnetizing Reagent Preparation.

Thirty five magnetizing reagents with various surfactant functional groups have been prepared for this study. The properties of these reagents were documented in the previous reports. Five reagents, selected from different cationic, anionic, and nonionic categories, were investigated for their shelf life. The results show that magnetizing reagents are stable for long term storage. There were no additional experiments performed during this period.

Task 2. Mineral/Reagent Interactions.

The interactions of magnetizing reagents and minerals under various conditions have been investigated. The conditions include pH, kinds and dosages of magnetizing reagents, mineral activator, coal depressant, and regulators. All of the experimental results have been described in the previous reports.

A series of new tests were performed during this period to determine the effects of pyrite oxidation on magnetizing reagent adsorption. Fine pyrite can be oxidized at a high rate. Since this task involves the use of -325 mesh pyrite, an investigation on the oxidation effect becomes necessary. As shown in Table 1, two groups of experimental results are compared. In the first group, pyrite prepared at -325 mesh for this study was conditioned directly with magnetizing reagent in water at pH 7. High magnetic susceptibility was obtained for each test. The second group of experiments was conducted by washing the pyrite with deionized water for five times. Then the filtered pyrite was conditioned with magnetizing reagent in water at pH 7. The results show that cationic magnetizing reagents are still adsorbed on pyrite but anionic and nonionic magnetizing reagents are not.

To understand whether the pyrite preparation procedure has defects, part of a washed and filtered pyrite sample was dried in an oven at 110°C for four hours. The dried pyrite was conditioned with magnetizing reagents in water at pH 7 immediately. The results are shown in Table 2. Drying in air obviously has caused the oxidation of pyrite. The oxidized pyrite releases ferrous sulfate into the solution and activates pyrite for the adsorption of anionic magnetizing reagents.

Task 3. Magnetite Size Effect.

The particle size of magnetite and its effects on the properties of magnetizing reagent were studied in this task. The experiments have been completed and the results were described in the previous reports.

Task 6. Coal Selection, Preparation, and Characterization.

This is the first task of the Phase II study, which is initiated during this reporting period. Three coals are selected: Ohio Lower Kittanning, Illinois No. 6, and West Virginia Pocahontas seams. The analysis of our inventory of coals from the three seams are:

<u>Coal Seam</u>	<u>Ash %</u>	<u>Pyritic SZ</u>	<u>Total SZ</u>
OH Lower Kit.	6.04	1.32	2.09
IL No. 6	10.83	1.48	3.68
WV Pocahontas	14.75	0.12	0.51

The basis for the selection of these three coals are: 1) Their ash contents vary in the range of interest; 2) Illinois No. 6 has both high pyritic sulfur and sulfate (gypsum) sulfur. Ohio Lower Kittanning is high in pyritic sulfur but low in sulfate sulfur. Pyritic and sulfate sulfur removal efficiencies can be compared from the two coals; 3) West Virginia Pocahontas is high in ash but low in pyritic sulfur. This allows a comparison on the separation efficiency between pyrite and other minerals.

After the approval of the selection, samples cut from freshly mined coals at 6" top size were purchased. The samples were shipped in a sealed container and received in late April. Processing and characterization of these samples are in progress.

Between the selection and receiving of the coals, the project is basically idling. To avoid the wasting of time for waiting, tests were conducted using our inventory coals to determine the possibilities of

separation with the proposed method. The inventory coals have been stored at a size of -28 mesh in plastic bags for four to five years. Serious oxidation has occurred. To avoid the high ferrous sulfate problem, each coal was washed with deionized water prior to the test. In each test, about 10 grams of coal screened at -70 mesh were conditioned with coal depressant and magnetizing reagent (MR-58 at 0.6 lb/Ton). The conditioned materials were fed through a magnetic separator twice at 3.5 kilogauss with a slurry velocity at 5.67 cm/sec. The cleaned coal was concentrated in the nonmagnetic fraction. After filtering and drying, the concentrate was analyzed for ash and sulfur forms.

The results of the tests are shown in Table 3. Reductions of ash and sulfur are significant. Sulfate sulfur removal in Illinois No. 6 is nearly completed. Pyritic sulfur removal may be comparable with heavy liquid separation at this size. (our data show Illinois No. 6 can yield cleaned coal of 0.56% pyritic sulfur and 70.24% weight recovery at 1.3 specific gravity for -28 mesh size). Ohio Lower Kittanning coal also shows that pyritic sulfur can be reduced from 0.67% to 0.22%. Ash reduction is less significant, as shown by the West Virginia Pocahontas coal. Since these tests use anionic type magnetizing reagent, the lower adsorbability on silicates can be expected. The use of cationic magnetizing reagents should be more effective for silicate removal.

Table 1. Enhanced magnetic susceptibility of pyrite with or without washing.

<u>Magnetizing Reagent</u>	<u>Function</u>	<u>Pyrite Without Washing</u>	<u>Pyrite Washed</u>
MR-1	cationic	48.5	56.4
MR-3	cationic	52.3	56.4
MR-30	anionic	40.5	2.3
MR-31	anionic	37.0	0.77
MR-35	anionic	43.2	1.0
MR-45	nonionic	49.1	0.94
MR-48	nonionic	46.6	3.4
MR-50	nonionic	32.5	1.3
MR-60	anionic	57.2	4.7
MR-80	cationic	40.2	39.7
MR-83	anionic	47.6	2.2
MR-89	cationic	57.0	60.5

Table 2. Effect of drying on pyrite oxidation
and magnetizing reagent adsorption.

<u>Magnetizing Reagent</u>	<u>pH</u>	<u>Magnetic Sus.</u> <u>(washed py. oven dried)</u>	<u>Magnetic Sus.</u> <u>(washed py. not dried)</u>
MR-1 (cationic)	3	53.1	22.4
	5	55.1	48.4
	7	53.3	59.8
	9	71.1	79.8
	11	53.6	24.6
MR-30 (anionic)	3	23.6	43.9
	5	32.3	3.4
	7	21.7	2.3
	9	3.9	1.7
	11	1.5	2.3
MR-31 (anionic)	3	18.8	2.2
	5	32.5	1.4
	7	27.4	1.6
	9	20.4	1.1
	11	1.0	1.2
MR-45 (nonionic)	3	57.0	54.8
	5	58.8	28.5
	7	53.9	1.7
	9	5.7	1.5
	11	0.9	1.1
MR-60 (anionic)	3	40.1	--
	5	47.6	14.6
	7	43.2	9.1
	9	34.5	8.8
	11	4.2	5.6

Table 3. Preliminary separation tests on inventory coals.

Coal	Head (-70 mesh)			Coal Concentrate					
	Ash Z	Py SZ	Sulfate SZ	Org SZ	Wt Z	Ash Z	Py SZ	Sulfate SZ	Org SZ
OH Lower Kit.	3.99	0.67	0.02	0.76	86.61	2.24	0.22	0.01	0.67
IL No. 6	11.39	1.08	0.31	1.54	74.95	6.76	0.57	0.01	1.58
WV Pocahontas	7.74	0.12	0.01	0.55	86.19	6.59	0.10	0.01	0.54

**DATE
FILMED**

9/02/92