LIQUID CHROMATOGRAPHIC FRACTIONATIONS
OF MIXTURES OF POLYSTYRENE OLIGOMERS

TECHNICAL REPORT
SUBMITTED FOR REVIEW
24 MAY 1980

DISCLAIMER
This book was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise, does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

MICHAEL A. CURTIS, JAMES W. WEBB, DORIS C. WARREN,
VERNON O. BRANDT, FRANCIS G. GERBERICH,
K. B. RAUT, AND L. B. ROGERS

DEPARTMENT OF CHEMISTRY
UNIVERSITY OF GEORGIA
ATHENS, GEORGIA 30602

MASTER

PREPARED FOR THE
U.S. DEPARTMENT OF ENERGY
ASSISTANT SECRETARY FOR ENERGY TECHNOLOGY
OFFICE OF ENERGY RESEARCH
UNDER CONTRACT DE-AS09-76ER00854

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency Thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

DISCLAIMER

Portions of this document may be illegible in electronic image products. Images are produced from the best available original document.

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise, does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

Available from
National Technical Information Service
U.S. Department of Commerce
5265 Port Royal Road
Springfield, Virginia 22161

Price: Code A03

Microfiche: Price Code A01

Printed in the United States of America.

TABLE OF CONTENTS

	Page
Abstract	1
Introduction	1
Experimental	3
Apparatus	3
Chemicals	3
Procedures	4
Column Preparation	4
Calculations	6
Results	8
Preliminary Studies	8
Nitro and Silica Columns	9
Amino Column	10
Octadecyl Column	10
Cyano and Phenyl Columns	11
Quantitative Aspects	12
Discussion	13
Acknowledgment	16
References	17
Table 1	19
Table 2	20
Table 3A	22
Table 3B	23
Table 3C	24

TABLE OF CONTENTS (cont.)

	Page
Table 4	25
Figure Legends	26
Figure 1	28
Figure 2	29
Figure 3	30
Figure 4	31
Figure 5	32

ABSTRACT

Oligomer mixtures of 800, 2200, and 4000 molecular weight polystyrene have been fractionated using silica and bonded phase columns under similar conditions of solvent gradient and flow rate. Using a hexane/tetrahydrofuran gradient, the silica and nitro phases were best in that they separated 41 and 43 oligomers, respectively. At the other extreme, a phenyl bonded phase column gave virtually no resolution using a water/THF gradient and a cyano bonded phase column, using the earlier hexane/tetrahydrofuran system, resolved only 10 oligomers. Amino and octadecyl bonded phase columns gave results intermediate between these two extremes.

The strength of the solvent used to dissolve the sample was found to be of critical importance. Use of too good a sample solvent seriously degraded the attainable resolution.

When number average and weight average molecular weights for an 800 molecular weight polystyrene sample were calculated from the oligomer distribution, the silica column gave values which were most consistent with those reported from other methods.

INTRODUCTION

There is considerable interest in separating oligomers of polymeric systems. Much of the recent work has been concerned with polystyrene due to its sensitivity to ultraviolet detection and to the availability of well characterized samples. Thus,

polystyrene can serve as a model for future work on the fractionation of oligomers of other polymers.

The most extensive work on the separations of oligomers of polystyrene has been with supercritical fluid chromatography (SFC) (1-8). In a recent report (1) 49 oligomers in a 2200 molecular weight (MW) sample were separated by SFC; however, separation times were long (17 hours) and required special instrumentation. Separations of 18 oligomers by gel permeation have also been reported within 12 hours (9-11) using 2 meter long columns.

There has been relatively little work utilizing high performance liquid chromatography (HPLC) to separate polystyrene oligomers. Kirkland (12) reported the separation of about 12 oligomers on octadecyl column using acetonitrile at 50°C. However, since he used isocratic conditions, the first peaks to elute were poorly resolved and the last peaks to elute were broad. Advertising literature has indicated that either a silica column used with a hexane/tetrahydrofuran (THF) gradient (13) or a reverse phase (Zorbax^R ODS) column used with a methanol/THF gradient (14) were good systems for separating polystyrene oligomers.

One objective of this investigation was to compare different column packings and solvent combinations for the eventual optimization of the resolution of polystyrene oligomers. A second objective was to compare them with the results from SFC techniques and to provide a basis for separations of other polymers.

Finally, the number average molecular weight ($\bar{M}_n$) of a polystyrene standard having a nominal $\bar{M}_n$ of 800 was calculated from the oligomer distribution using methods previously reported (4, 15).

EXPERIMENTAL

Apparatus

Two Varian Model 8500 pumps, one equipped with a solvent programmer (Varian Instrument Division, Palo Alto, CA), were used to generate mobile phase gradients. Samples were introduced into the columns by means of an air-actuated six-port Valco valve, Model AC V-6UHPA (Valco Instrument Company, Houston, TX), having a 12.5 μ l sample loop. The detector was a Perkin-Elmer LC-55 variable wavelength detector (Perkin-Elmer Corporation, Norwalk, CT) set at 265 nm. Chromatograms were recorded using a Sargent Model SR recorder (Sargent Welch Scientific Company, Skokie, IL).

Chemicals

Hexanes (a mixture of hexane isomers) and methyl alcohol, both J. T. Baker reagent grade, were used as mobile phases as received. Isopropanol, chloroform (both J. T. Baker reagent grade) and tetrahydrofuran (Fisher, histological grade) were used as packing solvents as received. Tetrahydrofuran (THF) that was used as a mobile phase or to dissolve the samples was distilled over 5:1 potassium-sodium alloy to remove water and

butylated hydroxytoluene. The latter had been added to the THF as a stabilizer. Water, used both as a mobile phase and a packing solvent, was deionized, then doubly distilled. It was degassed by heating under a water-aspirator vacuum immediately prior to use.

Monodisperse polystyrene samples (800, 2200, and 4000 MW) were obtained from the Pressure Chemical Company (Pittsburgh, PA). Sample mixtures were prepared using the two Varian 8500 pumps and solvent programmer. Samples of the 800 MW polystyrene that were used on the amino, cyano, nitro, and silica columns were usually dissolved in a hexanes/THF mixture. The 800 MW polymer was dissolved in 1:99 THF/hexanes at a concentration of 25 mg/ml. However, all samples used with the octadecyl and phenyl columns were dissolved in pure THF at a concentration of 100 mg/ml. In all cases, new samples were prepared every two weeks.

Column packings were obtained from E. Merck Laboratories, Incorporated (octadecyl, amino), Waters Associates (phenyl), Whatman, Incorporated (silica, cyano), and Rainin Instrument Company (nitro). Physical data for the columns are given in Table 1.

PROCEDURES

Column Preparation

All columns were constructed from 316 stainless steel tubing (25 cm x 4.1 mm I.D., Alltech Associates, Arlington Heights, IL)

that had been washed with 6 M nitric acid, followed by distilled water, methanol, and finally, THF. Dry nitrogen was then blown through the tubing.

All columns, except the phenyl bonded phase, were packed at 4500 psi using a Micromeritics Model 705-P slurry packer (Micromeritics, Incorporated, Norcross, GA) and one of the Varian pumps. After the packing pressure had been reached, slurry was passed into the column until it was full. The column of phenyl bonded phase was dry packed using the conventional tap-and-fill method.

The packed columns were prepared for sample injection by passing 20-30 column volumes of distilled THF through at a rate of 1 ml/min and then ramping down the solvent composition at a rate of 5%/min until the mobile phase composition corresponded to that used for injection on that particular column.

Sample injection was done in the following manner. After the baseline had stabilized, the sample loop was filled. The air-actuated valve was then switched to the "sample" position and, at the same time, the solvent gradient was initiated. After 2.5 minutes, the valve was switched back to the "load" position.

For the silica column, the initial mobile phase composition was 3:97 THF/hexanes. After sample injection, the solvent gradient was increased at 0.2% THF/min until elution of the separated oligomers had occurred and the signal had returned to the baseline. For the amino, cyano and nitro columns, the initial

percentages of THF in the hexane/THF mobile phase were 1%, 3% and 5%, respectively. Elution was performed by increasing the concentration of THF at 0.2%/min until all of the sample had eluted.

For the octadecyl and phenyl columns, the initial solvent composition was 60:40 THF/water, and the percentage of THF was increased at 0.2%/min.

At the end of each run, the following reconditioning procedure was performed prior to the next injection. After the signal had returned to the baseline, the percentage of THF in the eluent was increased to 100% at 10%/min. Pure THF was then passed through the column for 10 minutes to insure complete elution of sample components. Then, the solvent gradient was decreased at 5%/min to the initial solvent composition where the baseline was allowed to stabilize before the next injection. For the octadecyl and phenyl columns, a faster downramp (10%/min) was used. During the entire injection, elution and regeneration sequence, the flow rate of the mobile phase was held at 1.0 ml/min for all columns.

Calculations

Peak retention volumes were calculated by multiplying the distance measured from the injection point to the peak by the flow rate and dividing by the chart speed. Reproducibility of retention volumes in triplicate chromatograms were generally within a range of $\pm 2.5\%$ or ± 2 minutes, whichever was smaller.

Chromatographic peak areas were measured using a Keuffel and Esser Model 62000 compensating polar planimeter. The total peak areas from each chromatogram were summed, and each peak area was reported as its percentage of the total area.

Since the chromatograms used for molecular weight determinations did not exhibit baseline resolution of all oligomers, two methods of determining peak area were used. In method A, a line drawn between the lowest point of the valley on each side of the peak served as the baseline. In method B, a vertical line was extended from the lowest point of the valley on each side of the peak through the envelope to the baseline of zero signal so as to include that portion of the envelope in the area for that peak.

Each polystyrene oligomer had a butyl end group resulting from the polymerization process in which butyllithium was added as an initiator (3-5, 15). Consequently, the molecular weight of an oligomer was determined by:

$$\underline{M_x} = 104\underline{n} + 58 \quad (1)$$

where n was the degree of oligomerization and M_x was the molecular weight of the oligomer.

The weight average (M_w) and number average (M_n) molecular weights for 800 molecular weight polystyrene were calculated from the oligomer distribution in a manner similar to that used by Klesper and Hartmann (4) and Altares (15). The relative

area of each peak was divided by $\underline{n}$, the degree of oligomerization; the resulting value was proportional to $\underline{N_x}$, the number of molecules of that degree of oligomerization. Thus

$$\underline{\bar{M}}_w = \frac{\sum \underline{N_x} \underline{M_x}^2}{\sum \underline{N_x} \underline{M_x}} \quad (2)$$

and

$$\underline{\bar{M}}_n = \frac{\sum \underline{N_x} \underline{M_x}}{\sum \underline{N_x}} \quad (3)$$

RESULTS

Preliminary Studies

It was found that the sample solvent composition was critically important to the success of the separation. Use of too strong a sample solvent tended to elute the sample rapidly without allowing it sufficient interaction with the stationary phase. This "wash off" effect was characterized by a sharply rising front followed by poorly resolved peaks. No such effect was observed on the octadecyl or phenyl columns.

The effect of sample solvent can be seen in Figure 1 where samples of 800 MW polystyrene in pure THF, 1:1, 1:3, and 1:9 THF/hexanes (1a through 1d, respectively) were injected on the nitro column. Plainly, a trend toward improved resolution occurred as the sample solvent strength was decreased. An effect of sample solvent on the resolution of mixtures of simple

compounds has been noted previously (17). Since the 800 MW sample was soluble in 1:99 THF/hexanes, this solvent was used for further work on the amino, cyano, nitro and silica columns.

The 2200 and 4000 MW polystyrenes were not soluble in 1% or even 5% THF. Although they could be dissolved with some difficulty in 1:9 THF/hexanes by warming and shaking for several minutes, a solvent mixture of 1:3 THF/hexanes was used because it dissolved the molecular weight polystyrenes more easily and, in addition, the resulting separations appeared to be identical to those obtained using the 1:9 composition. Hence, the 1:3 solvent mixture was used for all further work with the 2200 and 4000 MW polystyrenes on the amino, nitro and silica columns.

Another exploratory experiment tested the feasibility of substituting cyclohexane for the mixture of hexanes in the mobile phase. Using 800 MW polystyrene and the nitro column under otherwise identical conditions, the time required to elute all of the oligomers in the sample (approximately 12 minutes) was not changed but the resolutions of the peaks were seriously degraded. Seven broad peaks eluted over a large envelope instead of 15 peaks.

Nitro and Silica Columns

These columns gave excellent separations, resolving 15 and 14 oligomers, respectively, for the 800 MW polystyrene (see Figures 2a and 2b and Table 2), and 43 and 41 oligomers, respectively,

for the 2200 MW (see Figures 4a and 4b and Table 2). Approximately 40 oligomers were discernible with the 4000 MW polymer on these columns (see Figures 5a and 5b).

The peaks corresponding to higher molecular weight species in the 2200 and 4000 MW polystyrenes appeared on a "hump" or envelope that has been observed in other separations of polystyrenes involving supercritical fluid chromatography (1, 2, 3, 7). The hump is probably due to unresolved oligomers since the fractional change in molecular weight due to the addition of a monomer unit becomes progressively less.

There was also a marked difference in appearance between the separations of 2200 and 4000 MW polystyrenes. In the latter, the envelope constituted most of the area reflecting the fact that there were larger relative concentrations of the higher molecular weight oligomers present.

Amino Column

Separation of the 800 and 2200 MW polystyrenes resulted in 13 and 25 oligomers, respectively (Figures 3a and 4c). Peak symmetry tended to be poor with the amino column such that even the peaks for the 800 MW sample showed pronounced tailing. The poor peak symmetry was especially noticeable for the 2200 MW sample.

Octadecyl Column

Hexane could not be used as a mobile phase because the

800, 2200 and 4000 MW polystyrenes each eluted as one peak with the solvent front. However, using a water/THF gradient the 800 MW sample produced 16 peaks of which only the first three were baseline resolved (Figure 2c and Table 2). The remaining 13 peaks eluted on an envelope. The 2200 MW polystyrene gave 19 oligomers, the rest of the sample having eluted as a broad, unresolved band (Figure 4d and Table 2).

Substituting methanol for water in the eluent decreased the resolution of the 800 MW sample. Under the same gradient conditions as above, i.e., starting at 60:40 THF/methanol and increasing the THF at 0.2%/min, the sample eluted as one peak. Even when the gradient was initiated with 100% methanol and run isocratically for 10 minutes, the oligomers eluted rapidly and produced 8 poorly resolved peaks.

Cyano and Phenyl Columns

These columns were not investigated thoroughly since the initial results were not promising. For the cyano phase, the same solvents and gradient were used as with the silica column. The 800 MW sample showed about 10 oligomers (see Figure 3b). The first few peaks were sharp but resolution and peak symmetry degraded rapidly for the larger oligomers. There was an irregular envelope with no clear resolution of any oligomers of the 2200 MW sample. The phenyl column showed an unresolved hump for the 800 MW sample using the same solvents and gradient as used with the octadecyl column (see Figure 3c).

Quantitative Aspects

The 800 MW polystyrene was used to check molecular weight determinations since virtually all of the sample components were well resolved on more than one column. In order to extract quantitative information from the chromatograms, the following assumptions were made, based on earlier SFC work. First, the first two peaks to elute after the solvent peak from the 800 MW sample on the octadecyl column were not considered to be part of the oligomeric series of polystyrene since they were not consistent with the pattern of increasing area for the next four peaks in the polystyrene homologous series. Thus, the first peak so identified as an oligomer is numbered 1 in Figure 2c and Table 2.

Second, the first oligomer to elute was the dimer, based upon the work of Jentoft and Gouw (5) and Altares (15) who collected early fractions of a 600 MW polystyrene and found no monomer present. Each subsequent peak was assumed to be the next highest member of the oligomeric series.

Finally, there was assumed to be a direct proportionality between the absorbance at 265 nm and the concentration of each oligomer (15).

Relative peak areas of 800 MW polystyrene for the silica, nitro and octadecyl columns are given in Table 3. Relative areas calculated using method B were more consistent between the three columns. Furthermore, when the envelope areas were

included, oligomers 6 and 7 gave peaks with the largest relative areas on all three columns.

Table 4 gives calculated values for $\bar{M}_W$ and $\bar{M}_N$. Although the results show that $\bar{M}_W/\bar{M}_N$ ratios from all three columns were similar and below the maximum of 1.3 given by Pressure Chemical Company, the individual $\bar{M}_W$ and $\bar{M}_N$ values for the octadecyl column were lower than those for the nitro and silica columns. Again, the $\bar{M}_W$ and $\bar{M}_N$ values for the three columns showed better agreement using method B.

Pressure Chemical Company reported a number average molecular weight for the 800 MW polystyrene of $811 \pm 5\%$ that was calculated by vapor phase osmometry. Note that both the nitro and silica columns gave molecular weights that were highly consistent with those previous data.

DISCUSSION

The separations of 2200 and 4000 MW polystyrenes on the nitro and silica columns demonstrate the potential of liquid chromatography for resolving oligomeric mixtures. The chromatograms show resolution approaching that attainable with state of the art supercritical fluid chromatography but using commercially available equipment and involving much shorter separation times (80 minutes versus 17 hours).

In order to obtain reproducible results with the amino, cyano, nitro and silica columns, a small concentration of THF in the mobile phase was necessary to overcome the "displacement

effect" (19, 20) that occurs upon introduction of a polar solvent (THF) into a nonpolar mobile phase (hexanes). Otherwise, polar solvent adsorbs on the stationary phase initially resulting in little change in polarity of the mobile phase to which the remainder of the column is exposed. However, once the entire packing has been saturated, there is a sudden change in polarity of the mobile phase; any solutes eluted at that time are usually unresolved.

In some of our chromatograms this phenomenon took the form of elution of the first few oligomers followed by a sharply rising front plus two or three fused peaks. The displacement effect was overcome by using the minimum concentration of THF in the initial mobile phase that would eliminate the problem. For each column with which the hexanes/THF eluent was used, the minimum concentration of THF was found by trial and error.

In addition to eliminating the displacement effect, THF in the mobile phase also served to moderate the activity of the silica column (21). Saunders (22) has shown that mixed solvents, consisting of nonpolar solvents, such as n-alkanes, and small percentages of a moderately polar solvent, such as THF or acetonitrile, are superior to water-moderated solvents for controlling the activity of the stationary phase. This is due both to the difficulty of preparing and storing nonpolar solvents having a constant water content (21) and to the long reequilibration times required of such solvents (23).

For analysis of the 800 MW polystyrene, the octadecyl column gave results complementary to those obtained with the nitro and silica columns; i.e., the low molecular weight oligomers were better resolved by the former column while the higher molecular weight oligomers showed baseline resolution with the latter columns. This trend was also evident with the 2200 MW polystyrene in that the first few oligomers were baseline resolved with the octadecyl column whereas they were not as well resolved on the nitro and silica columns. However, the latter two gave a much larger number of peaks since the higher molecular weight oligomers in the hump were at least partly resolved. A mixture of the two phases (or two columns in series) is not a practical alternative because the different eluting conditions used for each column.

One difference between the separations of the 800 and 2200 MW can be seen in the retention data in Table 2. While the retention volumes for the first few oligomers in both the 800 and 2200 MW samples showed agreement on a given column, those of the higher molecular weight oligomers in the 800 MW sample did not agree with the retention volumes of the same species in the 2200 MW sample. This may reflect an effect of the high molecular weight oligomers on the retentions of the low molecular weight oligomers.

Finally, it should be noted that while the nitro and silica columns showed superior performance under the conditions used, a change in operating conditions (e.g., use of a non-linear

gradient) might have improved the performances of the other stationary phases.

ACKNOWLEDGMENT

We wish to thank Bruce Semonian for carrying out some of the preliminary experiments. We are indebted to the Division of Basic Energy Sciences, Department of Energy, for partial support of this study through Contract No. EY-76-S-09-854 and to the University of Georgia Graduate School for a Graduate Assistantship (to M. A. C.).

REFERENCES

1. E. Klesper and W. Hartmann, Eur. Poly. J., 14, 77 (1978).
2. E. Klesper and W. Hartmann, J. Polym. Sci., Part B, 15, 9 (1977).
3. E. Klesper and W. Hartmann, J. Polym. Sci., Part B, 15, 707 (1977).
4. E. Klesper and W. Hartmann, J. Polym. Sci., Part B, B15, 713 (1977).
5. R. E. Jentoft and T. H. Gouw, J. Polym. Sci., Part B, 7, 811 (1969).
6. R. E. Jentoft and T. H. Gouw, J. Chromatogr. Sci., 8, 138 (1970).
7. J. E. Conaway, J. A. Graham, and L. B. Rogers, J. Chromatogr. Sci., 16, 102 (1978).
8. T. H. Gouw and R. E. Jentoft, J. Chromatogr., 68, 303 (1972).
9. D. J. Harmon in Gel Permeation Chromatography, K. H. Altgelt and L. Segal (eds.), Marcel Dekker, New York, 1971, p.13.
10. Von W. Heitz and H. Ullner, Makromol. Chem., 120, 58 (1968).
11. Von W. Heitz, B. Bomer, and H. Ullner, Makromol. Chem., 121, 102 (1969).
12. J. J. Kirkland, Chromatographia, 8, 661 (1975).
13. Perkin-Elmer Advertising Brochure, 1976.
14. DuPont Instruments Advertisement, Anal. Chem., 50, 331A (1978).
15. T. Altares, J. Polym. Sci., Part B, 8, 761 (1970).
16. T. Altares, D. P. Wyman, and V. R. Allen, J. Polym. Sci., Part A, 2, 4533 (1964).

17. P. K. Tseng and L. B. Rogers, J. Chromatogr. Sci., 16, 436 (1978).
18. R. E. Majors, Anal. Chem., 45, 755 (1973).
19. R. P. W. Scott and P. Kucera, Anal. Chem., 45, 749 (1973).
20. H. Engelhardt and H. Eglass, J. Chromatogr., 112, 415 (1975).
21. H. Engelhardt, J. Chromatogr. Sci., 15, 380 (1977).
22. D. L. Saunders, J. Chromatogr., 125, 163 (1976).
23. J. J. Kirkland, J. Chromatogr., 109, 297 (1975).

Table 1
Physical Data for Chromatographic Columns

Packing	Source	Particle Size (μ)	Packing Solvent
Octadecyl	E. Merck	10	1:1 <u>i</u> -PrOH:MeOH
Amino	E. Merck	10	3:1 CHCl ₃ :THF
Silica	Whatman	10	H ₂ O
Nitro	Machery-Nagel	10	<u>i</u> -PrOH
Cyano	Whatman	10	1:4 MeOH:CHCl ₃
Phenyl	Waters	37-75	Dry-Packed

Table 2
Retention Volumes of Species in Polystyrene Samples
of Molecular Weights 800 and 2200 on Silica, Nitro
Bonded Phase and C-18 Bonded Phase Columns

Peak Number	Retention Volumes, ml					
	Silica		Nitro		Octadecyl	
	800 MW	2200 MW	800 MW	2200 MW	800 MW	2200 MW
1	3.48	3.5	3.34	3.3	9.8	10.0
2	3.81	3.6	3.54	3.5	12.7	12.0
3	4.15	4.0	3.75	3.7	16.1	15.8
4	4.54	4.5	4.00	3.9	20.0	19.5
5	4.99	4.9	4.28	4.3	24.3	23.2
6	5.57	5.5	4.62	4.7	28.6	27.1
7	6.10	6.1	5.02	5.1	32.7	31.3
8	6.76	6.8	5.47	5.6	37.1	35.5
9	7.79	7.7	5.95	6.3	41.2	39.7
10	9.30	9.0	6.55	7.0	45.2	43.5
11	11.08	10.5	7.27	7.8	49.1	46.9
12	12.95	12.0	8.15	8.9	52.5	51.1
13	14.98	13.9	9.21	10.2	55.9	54.9
14	17.53 ^a	15.9	10.42	11.7	59.4 ^a	57.8
15		18.0	11.67 ^a	13.0		61.1
16		20.3		14.8		64.4
17		22.7		16.7		66.9
18		25.2		18.7		69.9
19		27.7		20.9		72.1
20		30.8		23.2		
21		33.0		25.7		
22		35.8		28.0		
23		38.3		30.5		
24		41.0		33.2		
25		43.6		35.8		

Table 2, Continued

Peak Number	Silica		Nitro		Octadecyl	
	800 MW	2200 MW	800 MW	2200 MW	800 MW	2200 MW
26		46.2		38.2		
27		48.7		40.6		
28		51.2		43.2		
29		53.8		45.8		
30		56.1		48.2		
31		58.4		50.6		
32		60.7		52.9		
33		62.9		55.3		
34		65.0		57.4		
35		67.2		59.6		
36		69.3		61.8		
37		71.3		63.9		
38		73.4		65.9		
39		75.3		67.9		
40		77.3		70.0		
41		79.9 ^a		71.9		
42				73.7		
43				75.8 ^a		

a. No higher oligomers resolved.

Table 3A
Relative Peak Areas of 800 Molecular Weight
Polystyrene on the Silica Column

Peak Number	n	Method A		Method B	
		Area %	$\frac{N}{\bar{x}}^a$	Area %	$\frac{N}{\bar{x}}$
1	2	0.5	0.25	0.6	0.3
2	3	3.1	1.0	3.1	1.0
3	4	5.5	1.4	6.0	1.5
4	5	8.3	1.65	8.9	1.8
5	6	11.2	1.87	11.5	1.92
6	7	12.9	1.85	13.5	1.93
7	8	13.1	1.63	13.7	1.72
8	9	11.9	1.33	12.9	1.43
9	10	10.1	1.01	9.6	0.96
10	11	7.7	0.70	7.0	0.64
11	12	6.0	0.50	5.1	0.43
12	13	4.4	0.34	3.7	0.31
13	14	2.9	0.21	2.4	0.17
14	15	2.3	0.15	1.9	0.13
15	16	b		b	

a. $\frac{N}{\bar{x}} = \% \text{ area}/n$

b. Not found on this column

Table 3B
 Relative Peak Areas of 800 Molecular Weight
 Polystyrene on the Nitro Column

Peak Number	n	Method <u>A</u>		Method <u>B</u>	
		Area %	$\frac{N}{\Sigma x}$	Area %	$\frac{N}{\Sigma x}$
1	2	0.4	0.2	0.5	0.2
2	3	2.9	1.0	3.2	1.1
3	4	4.7	1.2	6.1	1.5
4	5	7.7	1.5	9.1	1.8
5	6	10.4	1.73	11.6	1.93
6	7	13.1	1.87	13.5	1.93
7	8	13.8	1.72	13.8	1.73
8	9	12.9	1.44	12.7	1.41
9	10	10.7	1.07	10.2	1.02
10	11	8.0	0.73	7.5	0.68
11	12	5.4	0.45	4.3	0.36
12	13	3.9	0.30	2.9	0.23
13	14	2.6	0.19	2.0	0.14
14	15	2.0	0.13	1.5	0.10
15	16	1.3	0.08	0.9	0.06

Table 3C
 Relative Peak Areas of 800 Molecular Weight
 Polystyrene on the Octadecyl Column

Peak Number	n	Method <u>A</u>		Method <u>B</u>	
		Area %	$\frac{N}{\bar{x}}$ ^a	Area %	$\frac{N}{\bar{x}}$
1	2	0.9	0.4	0.7	0.3
2	3	4.2	1.4	3.3	1.1
3	4	8.0	2.0	6.6	1.7
4	5	11.2	2.24	9.2	1.8
5	6	13.8	2.29	12.1	2.01
6	7	15.3	2.18	13.8	1.97
7	8	14.6	1.83	13.9	1.74
8	9	14.5	1.61	12.3	1.36
9	10	9.0	0.90	9.9	0.99
10	11	5.6	0.51	7.2	0.65
11	12	2.9	0.24	4.8	0.40
12	13	1.4	0.10	3.0	0.23
13	14	0.7	0.05	1.8	0.13
14	15	0.3	0.02	1.1	0.07
15	16	b		b	

a. $\frac{N}{\bar{x}} = \% \text{ area}/n$

b. Not found on this column

Table 4

Molecular Weights Calculated for 800 Molecular Weight
Polystyrene from Separations Obtained on Silica,
Nitro and Octadecyl Columns Using Two Different
Baselines for Calculating Areas

	Silica		Nitro		Octadecyl	
	A	B	A	B	A	B
$\bar{M}_W$	917	897	930	893	818	876
$\bar{M}_N$	806	795	821	786	727	770
$\bar{M}_W/\bar{M}_N$	1.14	1.13	1.13	1.14	1.12	1.14

FIGURE LEGENDS

1. Separations of 800 MW polystyrene on a nitro bonded phase column using different sample solvents. a) 100% THF, b) 1:1 THF/hexanes, c) 1:3 THF/hexanes, d) 1:9 THF/hexanes; Gradient: 5% THF in hexanes to 8% THF at 0.2%/min.
2. Separations of 800 MW polystyrene. a) nitro bonded phase, sample solvent: 1:99 THF/hexanes, gradient: 5% THF in hexanes to 8% THF at 0.2%/min; b) silica column, sample solvent: 1:99 THF/hexanes, gradient: 3% THF in hexanes to 7% THF at 0.2%/min; c) octadecyl bonded phase, sample solvent: THF, gradient: 60% THF in water to 75% THF at 0.2%/min.
3. Separations of 800 MW polystyrene. a) amino bonded phase, sample solvent: 1:99 THF/hexanes, gradient: 1% THF in hexanes to 13% THF at 0.2%/min; b) cyano bonded phase, sample solvent: 1:99 THF/hexanes, gradient: 3% THF in hexanes to 13% THF at 0.2%/min; c) phenyl bonded phase, sample solvent: THF, gradient: 60% THF in water to 68% THF at 0.2%/min.
4. Separations of 2200 MW polystyrene. a) nitro bonded phase, sample solvent: 1:3 THF/hexanes, gradient: 5% THF in hexanes to 23% THF at 0.2%/min; b) silica, sample solvent: 1:3 THF/hexanes, gradient: 3% THF in hexanes to 23% THF at 0.2%/min; c) amino bonded phase, sample solvent: 1:3 THF/hexanes, gradient: 1% THF in hexanes to 31% THF at 0.2%/min; d) octadecyl bonded phase, sample solvent: THF,

gradient: 60% THF in water to 85% THF at 0.2%/min.

5. Separations of 4000 MW polystyrene. a) nitro bonded phase, sample solvent: 1:3 THF/hexanes, gradient: 5% THF in hexanes to 23% THF at 0.2%/min; b) silica, sample solvent: 1:3 THF/hexanes, gradient: 3% THF in hexanes to 23% THF at 0.2%/min.

ABSORBANCE

ABSORBANCE

RETENTION TIME, MINUTES

ABSORBANCE