DOE/MC/26039--1

DE92 017580

METHANE OXIDATION OVER DUAL REDOX CATALYSTS

Quarterly Technical Progress Report
January 1-March 31, 1989

Kamil Klier, Richard G. Herman, and Zbigniew Sojka

Zettlemoyer Center for Surface Studies
and
Department of Chemistry
Lehigh University
Bethlehem, PA 18015

March 1989

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

Prepared for

U. S. DEPARTMENT OF ENERGY
Morgantown Energy Technology Center
Under Contract No. DE-FG21-89MC26039

MASTER

o/s
DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

METHANE OXIDATION OVER DUAL REDOX CATALYSTS

DE-FG21-89MC26039

ABSTRACT

Review and analysis of the literature data on electron transfer itself and electron transfer oxidation of alkyl radicals was done in order to understand the mechanism by which methyl radical can be oxidized to CH_3^+ and further substituted by OH^- to form methanol. This allowed to compare and classify the various possible reaction patterns, understand the mechanism and circumstances of operation of each of them and select those which can be involved in oxidation of methyl radical. As a result an approach that is complementary to catalytic test studies was proposed. It consists of investigation of a set of partial reactions which reproduce a whole catalytic cycle in order to prove the reaction mechanism.

Synthesis of new oxide catalysts of the delafossite type, containing concentrated double redox sites, was designed. Synthesis of hydrozincite as a starting material for the preparation of doubly doped zinc oxide was performed.

INTRODUCTION

The objective of this research is to develop the scientific background for direct catalytic methane oxidation to methanol over oxides that are doubly doped with transition metal ions. The desired process will consist of double redox mechanism, where one redox couple is utilized for activation of oxygen and another for the conversion of methyl radicals to carbocations via electron transfer reaction. The latter species can react with surface OH^- groups to form methanol. To establish and understand the mechanism of electron transfer (ET) oxidation of methyl radicals, the current theories of electron transfer have been reviewed together with the redox chemistry of transition metal ion/alkyl radical systems.

Two groups of the catalysts will be tested for activity and selectivity, one containing dispersed redox centers ($\text{Cu}^{\text{I}}/\text{Fe}^{\text{III}}/\text{ZnO}$, $\text{Cu}^{\text{I}}/\text{Ti}^{\text{III}}/\text{ZnO}$) and a second of delafossite-type oxides containing concentrated redox centers (CuFeO_2 , CuCoO_2 , CuCrO_2). A preparation method of the delafossite catalysts was designed. Synthesis of hydrozincite for the preparation of the high purity high surface area ZnO matrix to be doped with transition metal ions was performed.

RESULTS

Mechanistic classification of redox reactions of alkyl radicals with transition metal ions (TMI)

Interaction of alkyl radicals with TMI may lead to the formation of an alkyl-metal bond, electron transfer, or ligand transfer. In each of these cases the metal ion undergoes a formal change of oxidation state of one and an alkyl ion is formed as an intermediate species. Since the carbonium ions are thermodynamically unstable, the real reactions for these redox processes are usually more complex and the various types of reaction patterns need to be distinguished in greater detail. The general classification of the mechanisms of oxidation of alkyl radicals by TMI is based on:

- (i) Bonding of the radical or carbocation in the electron transfer process. This gives rise to two main classes of ET: an outer- and inner-sphere electron transfer. For organic electron transfer reactions an alternative description as non-bonded and bonded electron transfer is also used.
- (ii) position at which the TMI is attacked by the radical. If the attack is oriented directly to the ligand, a process with transition state of free radical nature occurs, and an atom transfer takes place. On the other hand, attachment of the alkyl radical to the metal ion results in an alkyl-TMI

intermediate that can further react in a variety of ways including oxidative elimination, displacement, solvolysis or substitution. The factors which favor a given type of mechanism were rationalized in terms of the ionization potential, the soft and hard base nature of the oxidized radical, the nature of TMI, the ability of the radical to form stable carbocations, the redox potential of the TMI, and the chemical nature of ligands and their coordination strength.

The following classes were distinguished:

1. Outer-sphere oxidation (nonbonded mechanism). In this mechanism for oxidation of an alkyl radical (R $\cdot$), the transition state in the rate limiting step leads directly to a cation as an intermediate which undergoes fast subsequent steps of hydrogen elimination and substitution (Fig.1). In the outer sphere mechanism the rates obey the Marcus equation [1] and steric effects are small. This mechanism dominates in the oxidation of alkyl radicals with low ionization potential. High redox potential of the TMI and strong and hard ligands also favor this mechanism.

2. Inner-sphere oxidation (bonded mechanism) is involved when the alkyl radical must enter the coordination sphere of the TMI as a necessary step for oxidation. No correlation exists between the redox potential of TMI and the rate of oxidation. Steric effects are large and the chemical nature of the radical is important. The standard reactions of this mechanism are oxidative elimination and oxidative substitution (Fig.1), which often constitute parallel routes. Oxidative elimination is a common process for alkyl radicals with available β -hydrogens, unstable carbocations, and with ligands that are strongly coordinated to the TMI. During this mechanism, the elimination process itself is almost simultaneous with electron transfer, and a distinct carbocation does not appear along the reaction path.

Oxidative substitution constitutes a general class of reactions which encompass four types of particular substitution reaction patterns: ligand substitution, oxidative solvolysis, oxidative displacement and atom transfer (AT) (Fig.1). These reactions occur via the ET mechanism, in which carbocations are short lived intermediates, and via the ligand transfer (LT) mechanism where the electron transfer is accompanied by the ligand transfer.

The importance of oxidative substitution increases as the alkyl-metal moiety becomes capable of carbonium ion stabilization. When substitution proceeds via solvolysis of an alkyl-metal intermediate, the process is described as oxidative solvolysis.

Ligand substitution ET mechanism consists of addition of an oxidized radical to one of ligands, possessing e.g. unsaturated carbon-carbon bond. This mechanism is often involved in oxidation of methyl radicals in systems containing large strongly bonded unsaturated ligands like phenantroline [2].

Two modes of oxidation occur during ligand transfer oxidation: an atom transfer (AT) and oxidative displacement. The AT pathway involves direct conversion of the alkyl radicals into substitution products. The transition state for this mechanism is free radical in nature and solvent polar effects are small. The oxidative displacement route generates a carbonium ion of sufficient integrity somewhere along the reaction coordinate (ET), which is

then substituted by one of ligands (LT). Thus, this process cannot be classified exclusively as an ET or an LT mechanism. The oxidative displacement process is particularly involved in the case where the oxidative elimination path is impossible, and it is often encountered in the oxidation of methyl radicals by TMI complexes with weakly bonded hard ligands [3].

The classification of all reactions patterns is summarized in Fig.1.

Implications for the heterogeneous oxidation of methyl radical

As implied by Fig.1, methyl radical formed by homolytic hydrogen abstraction from methane by $O^{\cdot -}$ active species can undergo several possible reactions. In the case of TMI oxide catalysts, taking into account the high ionization potential of the methyl radical (9.89eV), its hard base nature, and absence of β -hydrogen atoms, three kinds of substitution reactions are possible: inner-sphere ET oxidative displacement or ligand substitution and outer-sphere substitution process. The latter seems to be only possible in the case of TMI with a high oxidation potential and becomes more important if OH groups are readily available in the vicinity of TMI.

In the inner-sphere ET process the $CH_3^{\cdot +}$ ions can undergo either a ligand substitution leading to surface methoxy species

or oxidative displacement reaction

with direct methanol formation. The competition of these two processes will depend on a spatial arrangement of the $CH_3^{\cdot +}$, OH^- and O^{2-} species immediately after hydrogen abstraction, localization of the TMI acceptor level in relation to the methyl-oxygen antibonding orbital, and the strength of the OH-TMI bond; the weaker is the latter, the more probable is oxidative displacement.

The literature data indicate that Cu^+/Cu^{2+} and Fe^{2+}/Fe^{3+} are the most appropriate redox couples capable of catalyzing this process. The advantage of double redox copper-iron systems may consist of a synergetic action of copper, as the displacement center, and iron as the $CH_3^{\cdot +}$ oxidation center due to much easier methylation of Fe(III) in comparison with Cu(II) [4,5].

In order to verify the feasibility of the mechanism discussed above, a set of model reactions which reproduce a whole catalytic cycle were proposed. In each step the postulated active species and intermediates can be created externally, via appropriate chemical procedures, in order to prompt a desired type of reaction step. The following set of model reactions can be considered:

(i) oxidative displacement: reaction of $\text{Me}^{n+}\text{-OH}^-$ with $\text{CH}_3\cdot$ obtained in situ. The source of methyl radicals can be photolysis of $(\text{CH}_3)_2\text{Hg}$ or azomethane:

(ii) step-wise execution of the whole catalytic cycle:

Preparation of the catalysts

An apparatus consisting of a water bath, a peristaltic pump, a mechanical stirrer and a pH-meter was set up and calibrated. Hydrozincite was prepared as in Ref. [6] by precipitation at 85-90°C of zinc(II) nitrate by dropwise addition of 1M solution of sodium carbonate to increase the pH to the final value of 7.0. The precipitate was digested for 1.5 h, washed 10 times with distilled water, filtered and dried at room temperature for 2 days.

The delafossites CuFeO_2 and CuCrO_2 will be obtained by firing cuprous oxide prepared by thermal decomposition of high surface area CuO (prepared in a similar way as ZnO) with high surface area Fe(III) and Cr(III) oxides [7,8] in evacuated closed quartz vessels at 1050°C for 48 h. CuCoO_2 will be prepared by the exchange reaction between CuCl and LiCoO_2 [8]. The starting mixture will be pressed and heated in evacuated sealed silica tube for 4 days at 490°C.

REFERENCES

1. R.A. Marcus, Ann.Rev.Phys.Chem., 1964, 15, 155
2. K.L. Rollic, J.K. Kochi, J.Am.Chem.Soc., 1982, 104, 1319
3. C.L. Jenkins, J.K. Kochi, ibid, 1972, 94, 843
4. G. Ferraudi, Inorg.Chem., 1978, 17, 2506
5. D. Brault, P. Neta, J.Am.Chem.Soc., 1981, 103, 2705
6. P.B. Himelfarb, G.W. Simmons, K. Klier, R.G. Herman, J.Catal., 1985, 93, 442
7. R.D. Shannon, D.B. Rogers, C.T. Prewitt, Inorg.Chem., 1971, 10, 713
8. J.P. Doumerc, A. Wichainchai, A. Ammar, M. Pouchard, P. Hagenmuller, Mater.Res.Bull., 1986, 21, 745

FIGURE CAPTIONS

Fig. 1. Mechanistic classification of redox reactions of alkyl radicals with transition metal ions. ET stands for electron transfer, LT for ligand transfer, AT for atom transfer, L for ligand, TMI for transition metal ion, R for alkyl radical, $>C_1$ for alkyl radicals with more than one carbon atom and IP for ionization potential.

OUTER-SPHERE (NONBONDED) PROCESS

FIGURE 1

**DATE
FILMED
8/27/92**