DOE/PC/89761--T3

DE92 015780

QUARTERLY

TECHNICAL PROGRESS REPORT

Submitted to U. S. Department of Energy

GRANT TITLE: NQR-NMR Studies of Higher Alcohol
Synthesis Cu-Co Catalysts

GRANT NO: DE-FG22 89PC89761/1 (GSU: 5-5374)

STARTING DATE: 09-15-89

ENDING DATE: 09-14-91

PROJECT DIRECTOR: A. N. Murty
Physics Department

INSTITUTION: Grambling State University
Grambling, Louisiana 71245

RECEIVED
USDOE/PETC
SI JAN 22 PM 12:50
ACQUISITION & MANAGEMENT DIV.

U.S./DOE Patent Clearance is not required prior to the publication of this document.

A. N. Murty
Project Director

Jan 14, 1991
Date

MASTER

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

QUARTERLY TECHNICAL REPORT
Period - September 14 - December 15, 1990

This report summarizes the research results of our investigations on the "NQR-NMR studies of supported copper cobalt catalysts" project.

The motivation for the studies stems from the experimental observations of the earlier investigators (1,2) that the inter-atomic ratios of the metals in the catalyst system $\text{CuO-CoO-Cr}_2\text{O}_3$ significantly control the selectivity to methanol/Alcohols/hydrocarbons. Their observations are summarized in Figure 1.

Fig: I

Figure 1 : Selectivity as a function of composition in the ternary system $\text{CuO-CoO-Cr}_2\text{O}_3$.

In the copper rich field, methanol is obtained as the main product the activity going through a maximum for $\text{Cu/Co} \approx 4-5$ and $\text{Cu/Cr} \approx 2-3$ Fischer Tropsch Catalysts are obtained in the cobalt rich field. For intermediate compositions $1 \leq \text{Cu/Co} \leq 3$, $\text{Co/Cr} \geq 0.5$ a mixture of light alcohols $\text{C}_1\text{-C}_6$ is obtained with hydrocarbons as by products.

It is believed that the morphology of the metal clusters and the nature of the metallic charge distribution significantly in-

fluence the catalytic behavior as well as the magnetic properties of the catalyst. The primary intent of our study is to investigate the magnetic character of copper-cobalt catalysts and examine the relation between catalytic and magnetic properties of the catalyst. The results reported in the previous report (3) on the zero-field NMR spectra of a series of Cu/Co catalysts have been a serious concern due to the number of high frequency lines observed which did not fit the expected pattern (4). To further investigate this discrepancy, we have prepared again several catalysts in our laboratory here at Grambling State University and consultant Prof. Akundi at Xavier/Tulane University and scanned the NMR/NQR spectra and studied the magnetization characteristics at Howard University during the Summer 1990. Two undergraduate physics majors, Lenward T. Seals and Marcus L. Jefferson, made the magnetization studies using the vibration sample magnetometer system under the supervision of professor Arthur N. Thorpe, consultant to the project.

RESULTS AND DISCUSSION:

The observed frequencies of the NMR lines are presented in Table I and plotted in Figure II. The spectra reveal a considerable scattering of frequencies relative to the expected lines (4) (shown by the broken vertical line). All the spectra were scanned a minimum of three times each and the frequencies are found to be precise within ± 0.3 MHz. The samples differ either in composition (Cu/Co ratio) or in the methods of preparation and reduction. The FCC line (213 MHz) is generally observed in all the samples at the expected frequency within experimental errors while the fault lines (215.5, 218.4 MHz) and the HCP line (221 MHz) appear slightly

TABLE I (NMR LINE FREQUENCIES OF BIMETALLIC Cu-Co CLUSTERS)
(Cluster Size range 20 - 50 nm)

Samples	Non Conforming Lines	FCC	FAULT	FAULT	FAULT	HCP	Non Conforming Line ^c
Co (powder) (Lit. Values (4))	-----	213.0	215.5	217	218.4	221	
Cu/Co = 0.2 (G)	211.2	213.0	215.2	---	218.1	220.7	224.5
Cu/Co = 0.4 (X1) #7	210.7	213.0	-----	216.1	218.5	221.3	223.2 224.9 226
Cu/Co = 0.4 (X2) #12A	-----	211.8	214.1	-----	-----	-----	223.0 224.8
Cu/Co = 0.6 (X1) #8	-----	212.9	-----	216.4	218.1	220.1	222.5 224.5 226.2
Cu/Co = 0.6 (X2) #13A	211.1	-----	213.6	-----	-----	-----	222.5 225.0
Cu/Co = 0.8 (X1) #9	210.8	212.6	214.2	215	217.9	220.2	-----
Cu/Co = 1.4 (G)	210.8	213.0	-----	215.6	218.0	220.5	----- 224.0
Cu/Co = 2.0 (G)	210.7	212.7	-----	215.1	218.0	220.2	223.4
		(212.8 ±0.2)	(213.9 ±0.3)	(215.3 ±0.3)	(218.1 ±0.3) ±0.2	(221 ±0.3)	(223 ±0.5) (224.5 ±0.5)

(X1) Samples were reduced using Micromeritics chemisorption system-The sample temperature was raised to 400°C-soaked in H₂ atmosphere for 1 hour-evacuated-resoaked in H₂ - evacuated - procedure repeated until no drop in H₂ pressure occurred while soaking (about 6 cycles). (X2) samples were reduced in a continuous flow of hydrogen about 350°C for about 12 hours. All (G) samples were reduced like the (X2) samples. The starting nitrates for Grambling State University samples (G) obtained from Aldrich Chemical, Co., while Fischer Scientific, Co., nitrates were used in the preparation of Xavier University samples (X). Also sodium carbonate was used for precipitation at Grambling State University, while sodium hydroxide was used at Xavier.

FIG. II (NMR LINE FREQUENCY POSITIONS)

NC*: Non Conforming Lines

below the expected frequency. But the most important features is the consistent occurrence of high frequency lines in the range 222.5-226.5 MHz in almost all the samples. These lines do not fit the expected pattern nor were observed in our previous studies (5-7) on supported cobalt catalysts on ZSM-5, silica, Alumina, magnesia and titania. This leads us to believe that significant changes in the metallic charge distribution or drastic morphological modifications might be occurring in the bimetallic copper-cobalt clusters. These modifications seem to be sensitive to the ratio of the metals and method of preparation.

The existing data shows that bimetallic catalysts prepared from noble metal precursors, in general, do not indicate modifications in the electronic structures of their component metals. Individual metal atoms appear to retain their characteristic catalytic and electronic properties. The results appear to correlate better with geometric ensemble effects than with electronic effects. This is perhaps due to the similarity in the electronic structures of noble metals. However, electron effects are expected to be predominant when group VIII metals are alloyed with group IB metals such as Ru-Cu, Ni-Cu and Co-Cu etc. Recent studies on the physics of metal clusters shed some new light on the physical and chemical properties of such small aggregates of metal atoms (8,9). These aggregates are too large to be described as molecules and too small to resemble small pieces of crystal. Such clusters are found to behave as "giant atoms" exhibiting a "shell structure" like that of atomic nuclei. The structure changes with the addition of just one or a few atoms. The physical and chemical proper-

ties of such clusters can be described by the "jellium" model (9)- Thomson's plum pudding model where electron waves replace the electrons and a positive jelly or "jellium" replaces the pudding. The electrons are neither completely localized as in Ne nor completely itinerant as in Na. The clusters behave like Newton atoms-particles with "hooks" that enable them to couple with other atoms. In large clusters the itinerant nature of the electrons is evident, while in small clusters some directional bonding is expected and structural effects become more important. The size, morphology, the number and positions of the atomic cores of a cluster determine the number and energy of the itinerant electrons which govern the physical and chemical properties of the cluster. In general, it is found that shell effects are superposed on an $N^{-1/3}$ cluster size dependance where N is the number of delocalized electrons.

Based on this picture when there exists a distribution of particle sizes, as is expected in our case, a given sample is likely to contain clusters of different sizes and different compositions and hence different chemical and physical properties. Any change in the ratio of the cluster metals or in the method of preparation of precursor, drying calcination and reduction could significantly influence the nature of the clusters. This could be the main reason why different groups preparing IFP catalysts according to patent prescriptions have reported different results for activity and selectivity (2). It seems that unless the preparation procedures are stringently controlled, it becomes extremely difficult to reproduce identical cluster compositions.

Non conforming NMR lines observed in this study (Table I)

below the normal FCC line and above the HCP line could occur when the hyperfine field at the cobalt nuclear site changes either due to changes in the morphology of the clusters or perturbations in the metallic charge distribution of the clusters. The resonance frequency is given by $\omega = \gamma (H_{hf} \pm \Delta H_{hf})$ where H_{hf} is the hyperfine field at the nuclear site. The nature and extent of the perturbation ($\pm \Delta H_{hf}$) in the metallic charge distribution is dependant upon the number and composition of metal atoms in the cluster. Both seem to depend sensitively on the Cu/Co ratio, as well as on the method of preparation of the catalyst. Samples 7 and 12A (Cu/Co = 0.4), 8 and 13A (Cu/Co = 0.6) marked X1 and X2 were prepared by consultant Professor Akundi of Xavier University with the same starting precursors. But the first samples (X1) were reduced in a closed system (10) while the second set (X2) were reduced in a standard flow through arrangement. The two spectra show significant differences indicating the influence of the reduction procedure. All other samples marked (G) were prepared here in our laboratory following the procedure described by Mouaddib and perrichon (11). But for the scattering in the high frequency lines, the standard lines show no significant deviations. The changes in the frequencies of lines above normal HCP line could arise due to changes in Cu/Co ratio which might alter the metallic charge distribution of the cluster, and result in a modification of the hyperfine field at the Co nuclear site.

MAGNETIZATION STUDIES:

Table II shows the susceptibility values of the precursors.

The precursors were prepared by Coprecipitation of the nitrates with sodium carbonate at a pH of 7-8. The precipitate was thoroughly washed and dried at 80°C before calcination at 350°C for 16 hours.

Table II (Susceptibilities of Precursors emu/g.Oe $\times 10^{-6}$)

Sample		Sample	
Cu/Co = 0.2	3.2	Cu/Co = 0.2 Co/Cr = 0.5	5.6
Cu/Co = 0.8	50	Cu/Co = 0.8 Co/Cr = 0.5	38
Cu/Co = 1.4	38 (?)	Cu/Co = 1.4 Co/Cr = 0.5	65
Cu/Co = 2.0	65	Cu/Co = 2.0 Co/Cr = 0.5	49 (?)

Standard values (CRC Handbook)

Cr (52)	3.5	Cu (66.5) = -0.09	CoO (75)	65.3
Cr ₂ O ₃ (136)	14.4	Cu ₂ O (143) -0.14	Co ₂ O ₃ (166)	27.5
		CuO (79.5) 3.0	Co ₃ O ₄ (241)	30.6

Though there appear certain discrepancies, the susceptibility values show an increasing trend with copper concentration. If we assume that the precursor may contain a mixture of oxides of copper, cobalt and chromium, it seems that the contribution of cobalt-oxides to the moment is not significant. As suggested by earlier investigators (2, 11) it appears that cobalt is in a spinel structure (CuO + Co₂O₃) CuCo₂O₄ in the precursor. In ferromagnetic spinels such as Fe₃O₄ (FeO + Fe₂O₃) the moment arises essentially due to the divalent ferrous ions and that due to the ferric ions vanishes by virtue of the site symmetry (12). This also explains the reasons why we could not observe NQR signals for copper oxide in

the monovalent form (Cu_2O) either in the precursor or in the reduced samples. The hysteresis data presented in Table III indicates a decreasing trend in the percent reduction of cobalt as the copper concentration increases. This is to be expected since cobalt in a spinel stricture is generally hard to be reduced to metallic state while copper is easily reduced. The second important factor to be noted is the appreciable increase in the coercive field value as temperature is changed from Room to Liquid nitrogen. If the particles are too large, there will be very little change in the H_c value (5, 13). From Luborskey Curve for H_c verses particle diameter, we find the particle sizes in these catalysts are likely to be in the range 20-50 nm.

Table III (Magnetization data)

Sample	Saturation Magnetization	Percent Reduction	Rem/Satrn Jr/Js	Coercive field (Oe)	
	Js (emu/g)			Rm.	LN ₂
Cu/Co = 0.2	109	68	0.29	593	1118
Cu/Co = 0.4	96	59	0.31	574	919
Cu/Co = 0.6	75	46	0.15	477	888
Cu/Co = 0.8	64	40	0.29	440	632
Cu/Co = 0.1	63	40	0.32	679	1093

These results are presently being reconfirmed and refined for presentation at the ensuing three conferences (Abstracts enclosed).

1. American Association of Physics Teachers and American Institute of Physics Joint Winter meeting (Jan. 19-24, 1991, San Antonio, Texas. "NQR-NMR and Magnetic Character of Copper/Cobalt Higher Alcohol Synthesis Catalysts" by A. N. Murty, M. L. Jefferson* and L. T. Seals*, Physics Department, Grambling State University; M. A. Akundi, Physics Department, Xavier University, and A. N. Thorpe, Physics Department, Howard University.

2. Louisiana Academy of Sciences, 65th Annual meeting. (Feb. 7-9, 1991, Shreveport, LA). "NQR-NMR studies of Cu-Co-Cr higher alcohol synthesis catalysts" by A. N. Murty, Tess L. Hoard* and Marcus L. Jefferson*, Physics Department, Grambling State University.
3. Twelfth North American meeting of the Catalysis Society (May 5-9, Lexington, KY). "NMR-NQR characterization of supported cobalt-copper mixed alcohol synthesis catalysts" by A. N. Murty, T. L. Hoard* and M. L. Jefferson*, Physics Department, Grambling State University; M. A. Akundi, Physics Department, Xavier University; R. T. Obermyer, Physics Department, Penn. State University; Vijay T. John, Chemical-Engineering Dept., Tulane University, Uday S. Rao, U. S. Department of Energy, Pittsburgh Energy Technology Center.

*Participating Undergraduate Physics Students.

REFERENCES

1. Courty P., Durand D., Freund D., Sugier A. J. Mol. Catalysis 17. 241. (1982)
2. Xu Xiaoding, E. B. M. Doesburg and J.J.F. Scholten. Catalysis Today 2, 125 (1987).
3. Murty, A. N. Technical Progress Report. Sept. 14, 1990 DE-FG22-89PC 89762.
4. Toth L. E. and S. F. Ravitz. J. Phys. Chem. Solids. 24, 1203 (1963).
5. Murty, A. N., M. Seamster, A. N. Thorpe, R. T. Obermyer and V. U. S. Rao. J. Appl. Phys. 67, 5847 (1990).
6. Murty, A. N., A. A. Williams, R. T. Obermyer, V. U. S. Rao, and R. J. Gormley. "Studies in surface science and catalysis-catalysis 1987" Ed. J. W. Ward, PP 73-80. Elsevier science publishers. B. V. Amsterdam (1988).
7. Murty, A. N., A. A. Williams, R. T. Obermyer and V. U. S. Rao. J. appl. Phys. 61, 4361 (1987)
8. Marvin L. Cohen and Walter D. Knight. Physics Today 42, December (1990).
9. De Heer, W. A. Knight, W. D. Chow, M. Y. Cohen, M. L. Solid State Physics 40, 93 (1987) and J. Chem. Phys. 91, 3141 (1987).
10. Murty, A. N. DOE Technical Progress Report, Feb. 2, 1990.
11. Mouddib N. and V. Perrichon. Proc. 9th Int. Congr. Catal. 2, 521 (1988).
12. Ali Omar, M. "Elementary Solid State Physics". Addison Wesley Publishing Co. (1975).
13. Luborsky, F. E. J. Appl. Phys. 33, 1909 (1962).

ABSTRACT OF CONTRIBUTED PAPER TO BE
PRESENTED AT THE 1991 AAPT/APS WINTER MEETING

NQR-NMR and Magnetic Character of Copper/Cobalt Higher
Alcohol Synthesis Catalysts*

A.N. Murty[†], M.L. Jefferson and L.T. Seals, Physics Department, Grambling State University, Grambling, LA 71245, (318) 274-2258.

M.A. Akundi, Physics Department, Xavier University, New Orleans, LA 70125 (504) 483-7648.

A.N. Thorpe, Physics Department, Howard University, Washington, DC 20059 (202) 806-6255.

Copper and Cobalt are the key elements in Syngas Conversion Catalyst Systems used for higher alcohol synthesis. Their proximity and synergy sensitively control the selectivity and efficiency of the process. It is believed that their outer electronic charge distribution which is responsible for their electrical and magnetic properties might be governing their catalytic properties also. To examine the correlation between catalytic and magnetic properties, a series of copper cobalt catalysts (Co/Cu ratio 5:1 to 5:5) with and without a support were prepared. The Nuclear Quadrupole resonance spectrum of copper and (zero-field) Nuclear Magnetic Resonance Spectrum of Cobalt and Magnetization and Hysteresis Character of the catalyst were analyzed. Similar to the catalytic results, the magnetic results also were found to be very sensitive to the preparation technique. The results indicate possible electron exchange between copper and cobalt, and cobalt and the support Titania.

*This work is supported by Department of Energy grant DE-FG22-89PC-89762.

[†]Member AAPT

Possible Session Topic: Undergraduate Research Project in Material Science

My \$25 abstract fee has been sent to the Executive Office
"PAPER FOR POSTER SESSION"

LOUISIANA ACADEMY OF SCIENCES

Call for Paper Titles & Abstracts

ANNUAL MEETING - FIRST THURSDAY, FRIDAY AND SATURDAY OF FEBRUARY

READ ALL INSTRUCTIONS BEFORE TYPING. MAIL THIS FORM AND ONE COPY OF THIS FORM TO YOUR SECTION CHAIRPERSON BY NOVEMBER 1st FOR INCLUSION IN THE PROGRAM.

PLEASE NOTE: At least one of the paper's authors MUST be an Academy member.

MURTY, N. AKUNDI, TESS L. HOARD, MARCUS L. JEFFERSON. Physics Department, Grambling State University, Grambling, LA 71245. - NQR-NMR studies of Cu-Co-Cr higher alcohol synthesis catalysts*. -

The selectivity and conversion efficiency are sensitively controlled by the atomic proximity and ratios of the elements in the trifunctional syn-gas conversion catalyst systems. High Yield of methanol - in copper rich field, hydrocarbons - in cobalt rich field and higher alcohols - in the midrange were observed. With a view to understand the nature and function of the interatomic interactions, the catalysts were prepared with different atomic ratios and the Nuclear Quadrupole Resonance spectra of copper and Nuclear Magnetic Resonance spectra of cobalt were examined. The results indicate possible electron exchanges between cobalt and the cocatalyst copper and support chromia. -

*Work supported by U.S. DOE grant. DE-FG22.89 PC89762.

1. Compose an abstract that will fit within this area. The abstract must be double-spaced and typed with elite size type. Type clean: use carbon ribbon.
2. FOLLOW THE EXAMPLE ON THE REVERSE SIDE OF THIS SHEET.
3. Author(s): first or single author put last name first, others first name first. Give full first and last names. CAPITALIZE AUTHOR'S NAME(S). If multiple authors underline the name of person presenting the paper. End with a period
4. Follow author(s) immediately with address(es) including zip code. End with a period.
5. Type a dash (-) before title of abstract. Capitalize only first letter of first word in title except for proper nouns, etc. Type a dash (-) at end of title of abstract.
6. Start text on next line without indentation using entire width of box. Type entire abstract within rectangular box and do not type on or beyond bottom of the box. The abstract will appear as you submit it.

"to encourage research in the sciences and disseminate scientific knowledge"

ABSTRACT OF CONTRIBUTED PAPER TO BE PRESENTED AT THE
TWELFTH NORTH AMERICAN MEETING OF THE CATALYSIS SOCIETY

NMR-NQR Characterization of Supported Cobalt-Copper Mixed
alcohol synthesis catalysts.*

A.N. Murty, T.L. Hoard and M.L. Jefferson. Phys. Dept.,
Grambling State University, Grambling, LA 71245.

M.A. Akundi. Phys. Dept., Xavier Univ., New Orleans, LA
70125.

R.T. Obermyer, Phys. Dept., Penn State Univ., McKeesport, PA
15132.

Vijay, T. John. Chemical Engineering Dept. Tulane Univ.
New Orleans, LA 70125.

V.U.S. Rao. U.S. Dept. of Energy. Pittsburgh Energy Tech-
nology center, Pittsburgh, PA 15236.

Cobalt and copper are active elements in a family of cata-
lysts that can convert syngas to mixed alcohols. The
specific activity and selectivity are governed by the Co/Cu
atomic ratio and the proximity of the Co and Cu sites. The
unfilled d-shells which are responsible for the character-
istic magnetic properties of transition metals also influence
their catalytic properties. An interaction between the
metals and the support could cause morphological changes in
the metal crystallites or perturbations in the metallic
charge distribution. These effects can be examined through
nuclear magnetic resonance (NMR) and nuclear quadrupole
resonance (NQR) spectroscopic techniques.

A series of cobalt-copper catalysts with different Co/Cu
atomic ratios were prepared on titania and chromia supports.
Na was added as a promoter on some catalysts. The NQR
spectra of ^{63}Cu in the frequency range 20-40 MHz, and the
zero-field NMR spectra of ^{59}Co in the frequency range
200-225 MHz were investigated using a servo controlled,
self-quenched super-regenerative spectrometer. In addition,
magnetization and hysteresis measurements were performed.
The results indicate possible electron transfer between
cobalt and copper, as well as between cobalt and titania.

*This work is supported by U.S. Department of Energy grant,
DE-FG22 89 PC89762.

END

**DATE
FILMED
8/03/92**