QUARTERLY TECHNICAL PROGRESS REPORT 1
OCTOBER - DECEMBER, 1986

ENHANCED DURABILITY AND REACTIVITY FOR
ZINC FERRITE DESULFURIZATION SORBENT

By
Mahesh C. Jha
Linda K. Baltich
AMAX Research & Development Center
5950 McIntyre Street
Golden, Colorado 80403-7499

Prepared for
U. S. Department of Energy
Morgantown Energy Technology Center
P. O. Box 880
3610 Collins Ferry Road
Morgantown, West Virginia 26507-0880

DOE Contract No. DE-AC21-86MC23172
AMAX Project No. 80270

February 23, 1987

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

7/28/87
MASTER
20

TABLE OF CONTENTS

	<u>Page</u>
SUMMARY	1
INTRODUCTION	2
BACKGROUND	3
PROCESS CHEMISTRY	3
EFFECT OF REACTOR SIZE	3
PROJECT OBJECTIVES AND TECHNICAL APPROACH	5
GENERAL TECHNICAL APPROACH	5
ACCOMPLISHMENTS	6
TASK 1. EXPERIMENTAL TEST PLAN	6
TASK 2. SORBENT PREPARATION AND CHARACTERIZATION	6
TASK 3. BENCH-SCALE TESTING	7
REFERENCES	8
APPENDIX A	
EXPERIMENTAL TEST PLAN	9

SUMMARY

On September 30, 1986, the Department of Energy (DOE), Morgantown Energy Technology Center (METC), Morgantown, West Virginia, awarded a contract (No. DE-AC21-86MC23172) to AMAX Extractive Research and Development Center, Golden, Colorado (AMAX), for a research project entitled "Enhanced Durability and Reactivity for Zinc Ferrite Desulfurization Sorbent". The objective of this experimental test program is to identify and investigate methods for improving the reactivity and durability of the zinc ferrite sorbent to be used for desulfurization of hot coal gas in integrated gasification combined cycle (IGCC) or molten carbonate fuel cell (MCFC) applications. For the purpose of the present program, the reactivity of the sorbent may be defined as its sulfur sorption capacity at the breakthrough point in a bench-scale fixed-bed reactor. The durability may be defined as the ability of the sorbent to maintain its reactivity and other important physical characteristics such as size, strength, and specific surface area during 10 cycles of sulfidation and regeneration. Two sorbents, T-2465 extrudes and 1094-63 pellets, form the base case sorbents against which enhancement is to be judged.

The project is divided into five tasks:

- Task 1. Experimental Test Plan
- Task 2. Sorbent Preparation and Characterization
- Task 3. Bench-Scale Testing
- Task 4. Bench-Scale Test Analysis
- Task 5. Topical Report

This first quarterly progress report presents the progress made during the quarter (October 1986 to December 1986) in completing Task 1 and in starting work on Tasks 2 and 3.

INTRODUCTION

The U. S. Department of Energy (DOE), through its Morgantown Energy Technology Center (METC), has been investigating a number of advanced systems for producing electric power from large coal reserves available in the United States. One of the most promising of these systems uses integrated gasification combined cycle (IGCC) technology, which has been demonstrated successfully at the Cool Water plant,¹ with hot coal gas cleanup technology currently under development at METC and its contractor's facilities.² The goal is to develop contaminant control technologies that operate at temperatures and pressures compatible with those of the gasifier and the power generator (gas turbine or molten carbonate fuel cell). Such a system will eliminate requirements for expensive heat recovery equipment and efficiency losses associated with fuel gas scrubbing. Two such systems proposed by M. W. Kellogg Company and General Electric Company, respectively, have been selected by DOE for demonstration under the Clean Coal Technology Program.³

Sulfur control at high temperature and high pressure forms a major portion of METC's hot gas cleanup program. Sulfur control is important for both the protection of gas turbine or fuel cell components and compliance with environmental regulations. Research performed at METC and its contractor's facilities over the last several years has demonstrated that high temperature desulfurization can be accomplished using solid zinc ferrite sorbents which can remove reduced sulfur species from the coal gas to the 10 ppmv level or less and which can be reused for further sulfur removal after regeneration with air.² Both General Electric and M. W. Kellogg (KRW Energy Systems) plan to use zinc ferrite sorbents for high temperature desulfurization of coal gas before it enters the turbine.

During the course of cyclic sulfidation and regeneration, the zinc ferrite sorbent experiences severe chemical, physical, and thermal changes. There are concerns that these changes will ultimately cause deterioration in the performance of the sorbent during long cyclic use. Bench-scale test work performed at AMAX R&D under DOE/METC Contract No DE-AC21-84MC21168 has shown that the sulfur loading capacity of the sorbent decreases significantly after many cycles of testing.⁴ The sorbent also undergoes attrition, and its specific surface area decreases in most cases. It has been seen, however, that the deterioration in the performance of the sorbent and its physical characteristics is strongly influenced by the chemical composition of the sorbent and by the method used for its preparation.

It is the objective of the present contract (DE-AC21-86MC23172) to systematically investigate methods for enhancing the physical durability and chemical reactivity of the zinc ferrite desulfurization sorbent.

BACKGROUND

PROCESS CHEMISTRY

A fixed-bed reactor will be used for high-temperature desulfurization. The coal gas, containing about 1 percent H_2S , will enter the reactor at about 550°C . As the gas passes through the sorbent bed, H_2S will be removed according to the reaction:

Prior investigations have indicated that H_2S could be removed to a few ppm level in the exit gas until breakthrough occurs. This is consistent with the thermodynamics of Reaction 1.⁵

Sulfided zinc ferrite can be regenerated using a mixture of air and steam according to the reaction:

This permits reuse of the sorbent for multiple sulfidation and regeneration cycles. Reaction 2 is extremely exothermic and to avoid excessive temperature rise (above 800°C) that may adversely affect the porosity and reactivity of the sorbent, a large proportion of steam (80 to 92 percent) is used. Sulfur dioxide produced during regeneration of zinc ferrite can be treated with one of several processes available for sulfur dioxide control. The goal would be to recover the sulfur in an environmentally acceptable, resaleable, or readily disposable form.

EFFECT OF REACTOR SIZE

In a fixed-bed reactor, Reaction 1 starts at the entry end and gradually progresses to the exit end. Tests performed on laboratory-, bench-, and pilot-scale have confirmed that a sulfur gradient would exist from the entry end to the exit end of the bed. The sorbent particles at the exit end contains essentially no sulfur before breakthrough and very little sulfur at breakthrough (100 to 200 ppm H_2S in the exit gas). The sorbent particles on the entry end may or may not be saturated with sulfur, depending upon the total bed depth and the depth of the reaction front. Generally, the larger the total bed depth and the smaller the depth of the reaction front (faster kinetics), more is the chance that the sorbent particles towards the entry end of the reactor will be saturated with sulfur.

When the sorbent is saturated with sulfur, Reaction 1 has gone to completion. For a 100 percent pure zinc ferrite sorbent (no binders or modifiers), this would mean a 13.3 percent weight gain, a sulfur sorption capacity of 40 percent (40 grams sulfur captured by 100 grams of sorbent), and a sulfur analysis of 35 percent in the sulfided sorbent. In deeper beds (4 to 6 feet depth) used at METC or KRW, it has been possible to sulfidize the sorbent to the 25 to 30 percent sulfur range on the entry end, while

breakthrough has occurred on the other end with only 1 to 2 percent sulfur in the sorbent. This would amount to an average of about 15 to 20 percent sulfur for the total bed.

For the same sorbent in a smaller bed (18-inch bed depth used in past AMAX work and planned for the present program), sulfur analyses on the two ends of the bed at the breakthrough point would be more like 15 and 1 percent, respectively, for an average of about 8 to 10 percent. The results would, however, be the same if the entire bed was sulfided to saturation (H_2S concentration about the same in the exit gas as in the feed gas), and this number, of course, would be close to what can be expected in a tall commercial reactor.

The advantage of using a short bed (18 inches) and sulfidation to breakthrough only, as planned in the present program, is that it allows a quick and inexpensive method of comparing various sorbents prepared under different conditions. A more reactive sorbent would capture more sulfur at breakthrough. A more durable sorbent would maintain its physical integrity and reactivity to a greater extent, in comparison to a less durable sorbent, in 10 cycles of testing.

PROJECT OBJECTIVES AND TECHNICAL APPROACH

The prime objective of the program is to identify and investigate methods for enhancing the reactivity and durability of the zinc ferrite sorbent. The enhancement is to be judged by comparing the reactivity and durability of the sorbents to be prepared and tested in the present program with those of two base case samples.

The first base case sample is Sample T-2465, zinc ferrite extrudes produced by United Catalyst Incorporated and used in the process demonstration unit (PDU) test program at KRW Energy Systems. The second base case sample will be Sample 1094-63, zinc ferrite spherical pellets produced by AMAX for METC during the last contract.

For the purpose of the present program, the reactivity of the sorbent is defined in terms of:

- Sulfur sorption capacity of the sorbent at breakthrough.
- Sulfur sorption capacity of the sorbent at near saturation.

The durability of the sorbent may be defined as its ability to maintain the following in repeated cyclic (10 cycles) use:

- Physical characteristics such as strength, size, and surface area.
- Chemical characteristics such as sulfur sorption capacity.

GENERAL TECHNICAL APPROACH

The above objectives can be accomplished by a systematic investigation of the process variables that affect the reactivity and durability of the sorbents. Modifications in chemical composition, agglomeration techniques, and induration conditions will be used to prepare a large number (about 200) of sorbent samples. Those samples that meet the criteria of physical characteristics will be tested for reactivity in single particle kinetic studies. These studies, to be performed by the Chemical Engineering Department of Louisiana State University, will involve testing of about 50 samples. Out of these, 13 samples will be selected for multicycle testing in the bench-scale reactor at AMAX. Selected samples of fresh sorbent and sulfided and regenerated sorbents from different parts of the reactor will be analyzed to determine their reactivity and durability. A topical report will be prepared presenting the results and, if appropriate, making recommendations for further test work.

ACCOMPLISHMENTS

The program is divided into the following five tasks:

- Task 1. Experimental Test Plan
- Task 2. Sorbent Preparation and Characterization
- Task 3. Bench-Scale Testing
- Task 4. Bench-Scale Test Analysis
- Task 5. Topical Report

During the first quarter of the project (October 1986 - December 1986), progress was made towards completing Task 1 and initiating Tasks 2 and 3, as detailed in the following pages.

TASK 1. EXPERIMENTAL TEST PLAN

Soon after the award of the contract, work was started on preparation of the Experimental Test Plan. The purpose of this document is to describe how and why various test work will be performed to accomplish the project objectives. The exercise provides good thinking through opportunity. A draft copy of the Experimental Test Plan was sent to METC on November 6, 1986.

The plan was formally presented and discussed during the project kick-off meeting held at METC on November 20, 1986. Two key personnel, Mahesh C. Jha and Linda K. Baltich, made the presentation and participated in the discussions. Several useful comments and suggestions were made by METC personnel attending the meeting, particularly by Messrs. Ken Markel, Suresh Jain, and Thomas Grindley.

During the month of December 1986, the Experimental Test Plan was revised to incorporate the changes suggested at the METC meeting. The revised plan was submitted to METC on January 8, 1987. A copy of this document is included in Appendix A.

TASK 2. SORBENT PREPARATION AND CHARACTERIZATION

Purchase orders were placed for the raw materials required for preparation of the sorbents. These materials included pigment-grade iron oxide from Mobay Chemical, catalyst-grade iron oxide from United Catalyst, bentonite, Methocel, and starch.

The sorbent preparation equipment (bench-scale pelletizer and extruder) had not been used for quite some time. They were located, cleaned, and checked for proper functioning. The pelletizer was working well. The extruder needed a new motor, for which a purchase order was placed.

Characterization of sorbent will include measurement of bulk density, crush strength, attrition resistance, specific surface area, and porosity. A graduated cylinder

will be used for measurement of bulk density. A new Chatillon tension and compression tester was acquired for measuring crush strength. A rolling drum type apparatus has been designed following ASTM guidelines for determining the attrition resistance of the sorbent samples. The apparatus is presently under construction. The instrument for BET specific surface area measurement (Quantasorb system made by Quantachrome Corporation) was checked and found to be in working order. Porosity measurement will be made on selected samples by an outside laboratory (Coors).

TASK 3. BENCH-SCALE TESTING

In order to screen a large number of sorbent samples for their reactivity, it is planned to perform single particle kinetic studies on them. After receiving the notification of contract award from METC, Professor Douglas Harrison of the Chemical Engineering Department at Louisiana State University was contacted in October 1986. He submitted a proposal on November 10, 1986, to perform single particle kinetic studies on a subcontract basis. The proposal was reviewed and approved by AMAX in December 1986. A formal contract between AMAX and LSU was signed on January 5, 1987.

The bench-scale reactor system used in past AMAX work was disassembled, inspected, cleaned, modified, and reassembled. Since the gases are corrosive and the apparatus had been used for over an year during the last project, it was decided to replace all the valves and fittings on the gas feed and exit lines. Other major modifications include:

- Installation of a smaller size thermowell to minimize any chance for channeling. This thermowell now contains only three thermocouples measuring bed temperatures at the top, middle, and bottom.
- Installation of new larger size preheaters that will not get plugged with deposited carbon during a test run.
- Installation of a microcomputer (AMAX property) to collect, display, and record important test data such as temperatures, pressure drop, and H_2S and SO_2 concentration as a function of time during any test cycle. To accommodate the input of gas composition, the gas chromatograph has to interface with the computer. This work was initiated during the first quarter and will be completed next quarter.

One of the base case samples, Sample T-2465, was requested and received from METC. The other base case sample, 1094-63, is already available at AMAX.

Purchase orders were placed for gas cylinders.

REFERENCES

1. T. P. O'Shea, "Electric Power from Coal-Derived Gas", Chemical Engineering Progress, August 1984, pp. 71-76.
2. K. E. Markel and D. C. Cicero (Editors), Proceedings of the Sixth Annual Contractors Meeting on Contaminant Control in Coal-Derived Gas Streams, DOE/METC-86/6042, Morgantown Energy Technology Center, P. O. Box 880, Morgantown, West Virginia 26507, June 1986.
3. Anonymous, "CCT Negotiations Begin", Coal & Synfuels Technology, Volume 7, No. 29, August 4, 1986.
4. M. C. Jha, M. T. Hepworth, and L. K. Baltich, "Enhanced Sorbent Durability for Hot Coal Gas Desulfurization", Report DOE/MC/21168-2023, Final Report prepared by AMAX Extractive Research and Development Center, Golden, Colorado, for Morgantown Energy Technology Center under Contract No. DE-AC21-84MC21168, March 1986.
5. T. Grindley and G. Steinfeld, "Zinc Ferrite Hydrogen Sulfide Absorbent", in Third Annual Contaminant Control in Hot Coal Derived Gas Streams Contractors Meeting Proceedings, K. E. Markel (Editor), DOE/METC/84-6, Morgantown Energy Technology Center, Morgantown, West Virginia, December 1983, pp. 145-171.

APPENDIX A
EXPERIMENTAL TEST PLAN

**ENHANCED DURABILITY AND REACTIVITY FOR
ZINC FERRITE DESULFURIZATION SORBENT**

(Contract Number DE-AC21-86MC23172)

EXPERIMENTAL TEST PLAN

Prepared for
U. S. Department of Energy
Morgantown Energy Technology Center
3610 Collins Ferry Road
Morgantown, West Virginia 26505-0880

By
AMAX Extractive Research and Development Center
5950 McIntyre Street
Golden, Colorado 80403-7499

Revised and Submitted in Final
Form on January 8, 1987

TABLE OF CONTENTS

	<u>Page</u>
INTRODUCTION	1
PROGRAM BACKGROUND	2
GENERAL TECHNICAL APPROACH	3
METHODS FOR IMPROVING DURABILITY AND REACTIVITY	3
PRIMARY VARIABLES	4
Zinc/iron Stoichiometric Ratio	4
Grade of Iron Oxide	4
Type and Amount of Binder(s)	5
Sorbent Shape	5
INDURATION CONDITIONS	5
SECONDARY VARIABLES	6
Type and Amount of Substitute Binders	6
Type and Amount of Modifiers	6
TEST MATRIX	8
TASK 2. SORBENT PREPARATION AND CHARACTERIZATION	11
SORBENT PREPARATION	11
SORBENT CHARACTERIZATION	11
TASK 3. BENCH-SCALE TESTING	12
SINGLE PARTICLE KINETIC STUDIES	12
Experimental Setup	12
Test Procedures	12
Test Conditions	15
BENCH-SCALE TESTS	16
Apparatus and Instruments	16
Test Procedures	18
Test Conditions	19
TASK 4. BENCH-SCALE TEST ANALYSIS	21
DATA ACQUISITION AND ANALYSIS	21
PHYSICAL ANALYSES	21
CHEMICAL AND MINERALOGICAL ANALYSES	22
REFERENCES	23

LIST OF TABLES

		<u>Page</u>
Table 1.	Summary of Test Variables and Responses to be Investigated	8
Table 2.	Test Levels for Primary Variables	9
Table 3.	Statistical Screening Design Test Matrix	9
Table 4.	Recommended Test Conditions for Single Particle Kinetic Studies	15
Table 5.	Planned Test Conditions for Bench-Scale Tests	20

LIST OF FIGURES

Figure 1.	Schematic flow chart for the proposed test program.	10
Figure 2.	Diagram of the apparatus for single particle kinetic studies.	13
Figure 3.	Gas feed manifold.	14
Figure 4.	Schematic diagram of bench-scale test apparatus.	17

INTRODUCTION

An experimental test program, "Enhanced Durability and Reactivity For Zinc Ferrite Desulfurization Sorbent", has been started at AMAX Extractive Research and Development Center under METC Contract Number DE-AC21-86MC23172. The objective of this program is to identify and investigate methods for improving the reactivity and durability of the zinc ferrite sorbent to be used for desulfurization of hot coal-gas in integrated gasification combined cycle (IGCC) or molten carbonate fuel cell (MCFC) applications.

The program is divided into the following six tasks:

- Task 1. Experimental Test Plan
- Task 2. Sorbent Preparation
- Task 3. Bench-Scale Testing
- Task 4. Bench-Scale Test Analysis
- Task 5. Topical Report
- Task 6. Additional Testing

This document, "Experimental Test Plan", is being submitted to METC as part of the deliverables under the contract. It presents and discusses why and how various test work will be performed to accomplish the project objectives.

PROGRAM BACKGROUND

A fixed-bed reactor will be used for high-temperature desulfurization. The coal-gas containing about 1 percent H_2S will enter the reactor, and as it passes through the bed, H_2S will be removed according to the reaction:

Prior investigations have indicated that H_2S could be removed to a few ppm level in the exit gas until breakthrough occurs. It will be desirable that the sorbent have a high sulfur sorption capacity on a weight percent basis. The sorbent will be regenerated by a counter-flow of air and steam mixture to produce a rich SO_2 gas stream according to the reaction:

The regenerated sorbent in the reactor will now be ready for the next sulfidation cycle.

A zinc ferrite sorbent (Sample T-2465), produced by United Catalyst Incorporated (UCI) and used in the process demonstration unit (PDU) test program at KRW Energy Systems, has been designated the base case sorbent for the present AMAX program. In addition, AMAX sorbent pellets produced for METC will be tested as another base case.

The goal of our work is to identify and investigate methods that could be used to produce a sorbent(s) with better reactivity and durability than the base case sorbents. Both of these characteristics will affect the economics of the desulfurization process.

For the purpose of the present program, the reactivity of the sorbent may be defined in terms of:

- Sulfur sorption capacity of the sorbent at breakthrough.
- Sulfur sorption capacity of the sorbent at near saturation.

The durability of the sorbent may be defined as the ability of the sorbent to maintain the following in repeated cyclic use.

- Physical characteristics such as strength, size, and specific surface area.
- Chemical characteristics such as sulfur sorption capacity.

Based on past experience, it is projected that a comparative evaluation of durability can be made by testing sorbents for 10 cycles.

GENERAL TECHNICAL APPROACH

Modifications in chemical compositions, agglomeration techniques, and induration conditions will be used to prepare about 200 sorbent samples (Task 2). Those samples that meet the criteria of physical characteristics will be tested for reactivity in single particle kinetic studies. The sorbent samples found to possess superior reactivity will be tested in the bench-scale reactor for 10 cycles. The base program calls for testing 15 sorbents (Task 3). Selected samples of fresh sorbent and sulfide and regenerated sorbents from different parts of the reactor will be analyzed to determine their reactivity and durability (Task 4). A topical report will be prepared to present the results and, if appropriate, make recommendations for further test work under Option 1. After approval by the Contract Officer's Technical Representative (COTR), additional sorbent samples (up to 15) will be prepared and tested (Task 6). One cubic foot of the "best" sorbent will be produced and shipped to METC for independent testing.

METHODS FOR IMPROVING DURABILITY AND REACTIVITY

Our past experience with sorbent production and testing has indicated that many variables affect the durability and reactivity of the zinc ferrite sorbent. In general, they can be grouped into two categories:

1. Chemical Composition
2. Physical Characteristics

The main variables in the area of chemical composition are the concentrations of zinc and iron oxides and the amount of any chemical modifiers added. In terms of physical characteristics, the important parameters are agglomerate size and shape, crush strength, specific surface area, and porosity.

The overall goal is to produce a sorbent with a strong porous structure that allows hydrogen sulfide gas to easily penetrate the pores of the sorbent for fast reaction on a large surface, thus improving the reactivity under the design constraints of a fixed-bed reactor. The strength is important to assure that the sorbent does not disintegrate under the weight of the bed, leading to increased pressure drop and, more importantly, loss of sorbent fines in the exit gas. The durability of the sorbent implies that this porous and reactive structure is maintained in long-term cyclic testing, even though the sorbent undergoes severe chemical and structural changes (sulfide and oxide formation) between the sulfidation and regeneration cycles.

These important chemical and physical characteristics of the sorbent can be changed by changing one of the many process variables during the production of the sorbent. These variables can be grouped into three classes:

1. Primary Variables
2. Induration Conditions
3. Secondary Variables

The following paragraphs discuss the specific details for each variable.

PRIMARY VARIABLES

The following are the primary variables that affect the reactivity and durability of the sorbent.

1. Zinc/Iron Stoichiometric Ratio
2. Grade of Iron Oxide
3. Type and Amount of Binder(s)
4. Sorbent Shape

The general effect of each of these variables is discussed below, along with our reasoning as to what we would like to investigate in the present program and why.

Zinc/Iron Stoichiometric Ratio

Past work done at METC¹ and AMAX² have indicated that pure zinc oxide or higher than stoichiometric amounts of zinc oxide in zinc ferrite result in inferior performance in comparison to stoichiometric zinc ferrite or a slight deficiency of zinc oxide. This may be due to the formation of an impervious zinc oxide layer on macro or micro-scale when an excess of zinc is present. We would like to determine this effect by testing two zinc/iron stoichiometries: 1.0 and 0.8.

Grade of Iron Oxide

One of the main reasons for selecting zinc ferrite over zinc oxide may be the abundance of iron oxide. In both Japan and the United States, iron oxide alone has been investigated for hot coal-gas desulfurization application. One limitation in that case is that the H₂S concentration level cannot be brought down to a few ppm level required for molten carbonate cell application.¹ The level, a few hundred ppm, may be acceptable in IGCC application.

However, during past work on this project, we found out that there are several grades of iron oxide available in the market, and they vary in price from about \$0.05/pound to about \$4.00/pound. Also, the sorbent produced from these different types of iron oxides had very different reactivities. It is partly related to particle size or specific surface area and partly to process conditions used in their production.

In any case, we would not recommend investigating mineral-grade iron oxide any further because of the poor reactivity observed in our last program, even though this grade may be the least expensive.² Both pigment grades (produced by Mobay Chemical) and catalyst grades (produced by United Catalyst) were found suitable. We will compare them in a definitive manner by producing sorbents using these two types of iron oxides. If the two perform about the same, the less expensive pigment-grade iron oxide will be used in all further work.

Type and Amount of Binder(s)

An organic binder, Methocel, was used by United Catalyst Inc. (UCI) as an extruding aid in producing zinc ferrite extrudes used in earlier work at METC. While the surface area of these sorbents was high and initial reactivity good, they disintegrated very easily to fines and also lost their porosity in repeated cyclic testing. This is probably because Methocel burned away during the heat treatment of the sorbent, leaving behind a porous structure, but there was no permanent bond to keep the structure intact when chemical and structural changes took place.

The use of inorganic binders such as bentonite overcomes this problem and results in a durable sorbent, as shown by our work in the previous contract. Based on those results, METC recommended that UCI use 2 percent bentonite as the binder in the production of zinc ferrite extrudes to be tested at KRW Energy Systems. This sorbent (Sample T-2465) would be the base case sorbent for our present program. The rationale for using a low amount of bentonite, which is almost as expensive as zinc or iron oxide, is minimization of an inert diluent and, therefore, greater reactivity. We, however, think that a higher amount (probably 5 and maybe even 10 percent) may be better in terms of durability and maintaining the reactivity for long periods. This issue can be resolved by investigating bentonite addition at 3 and 10 percent.

As discussed above, organic and inorganic binders may serve two distinct functions, and towards the end of our last project, we investigated a combination of the two types of binders in hope of combining the two desired properties, strength and porosity, in the sorbent. The results indicated that it worked. However, within the scope and budget of that project, we could not systematically investigate this point. In the current program, the organic binders, methocel and starch, will be examined for extrudes and pellets, respectively. Sorbent samples containing bentonite with and without an organic binder will be tested.

Sorbent Shape

Both cylindrical extrudes and spherical pellets have been used in our past project. United Catalyst has prepared sorbents by the extrusion method, which is standard in the preparation of catalysts for the petrochemical industry. AMAX prefers to use a disc pelletizer, which is widely used to produce strong iron ore pellets for the steel industry. Spherical pellets are probably preferable from the handling point of view and may produce a more uniform gas flow pattern. Also, stresses caused by structural changes during cyclic sulfidation and regeneration are more likely to break randomly packed cylindrical extrudes in comparison to spherical pellets. Both sorbent shapes will be examined during the present program.

INDURATION CONDITIONS

Agglomerates produced by either pelletizing or the extrusion method have to be indurated at high temperatures to impart them with the proper combination of strength

and porosity. The important parameters are temperature and time. Based on past experience of producing close to 200 sorbent samples during the last two years, we know that the chemical composition and agglomeration conditions used in the preparation of green agglomerates strongly influence the time and temperature of induration that would result in proper physical properties of the sorbent.

The most practical approach is to produce a batch (about 20 pounds) of the sorbent of fixed chemical composition under selected agglomeration conditions and then indurate portions of this sample at different temperatures (generally in the range of 1,500 to 1,900°F) for different times (15 minutes to 4 hours). The indurated samples are then characterized for their bulk density, which is a good indicator of their porosity. The samples that meet this criterion (a bulk density of below 1.5 and preferably under 1 for spherical pellets) are tested for their crush strength.

Once the induration conditions have been established for a given chemical composition and agglomeration conditions, the remaining sample will be prepared for further testing by the single particle kinetic study or in the 2-inch diameter bench scale reactor.

SECONDARY VARIABLES

The following are considered to be secondary variables. These variables will be studied for the best sorbents developed based on the primary variables.

1. Type and Amount of Substitute Binders
2. Type and Amount of Modifiers

The general effect of these variables is discussed below.

Type and Amount of Substitute Binders

The use of bentonite was proven effective in the previous program as an inorganic binder. However, several tests were also performed using kaolin in place of or in addition to bentonite. These sorbents behaved satisfactorily, but kaolin addition was not studied conclusively in the previous program. Once the addition level of bentonite is determined in the current program, kaolin addition will be studied as a replacement. In the same manner, molasses will be studied as an alternative to starch as an organic binder for pellets.

Type and Amount of Modifiers

Desulfurization is a chemical reaction and reactivity is related to kinetic mechanisms. There were indications in our past work that the formation of an impervious zinc oxide layer on some sorbent surfaces may be slowing down the diffusion of sulfur or oxygen species and thereby reducing reactivity. A search of literature indicated that the presence of certain alkali metal compounds, even in very small

concentrations, enhances the diffusivity by several orders of magnitude.³ There also has been a suggestion that reactions involving zinc oxides and zinc sulfides can be catalyzed.⁴ Both sodium carbonate and molybdenite were present in small amounts in the best sorbent we have produced to date. We plan to investigate the effect of sodium carbonate and molybdenite additions individually.

The pigment-grade iron oxide (produced by Mobay Corporation) used in the production of our best sorbent contained about 3 percent manganese. We suspect that the presence of manganese was partly responsible for the superior performance of the sorbent. This speculation is based on published results of some of the earlier work performed at Louisiana State University (LSU) indicating that manganese oxide is a good desulfurizing agent.⁵ A manganese oxide based sorbent was also investigated by U. S. Steel Corporation.⁶ To determine the possible beneficial effect of the presence of manganese, we propose to investigate the performance of a manganese free, pigment-grade iron oxide with and without manganese oxide (commercial) addition. We will also investigate the addition of copper in small amounts.

TEST MATRIX

Table 1 summarizes the variables to be investigated in the program. There are five primary variables to investigate and six secondary variables. In addition, induration time and temperature will be investigated for each type of sorbent prepared in order to select those conditions that result in the preparation of the sorbent with acceptable physical properties.

Table 1. Summary of Test Variables
and Responses to be Investigated

Primary Variables

Grade of Iron Oxide
Zn/Fe Ratio
Bentonite Addition Level
Organic Binder Addition
Sorbent Shape

Induration Conditions

Induration Time
Induration Temperature

Secondary Variables

Sodium Carbonate Addition
Molasses as Organic Binder
Kaolin Addition as Replacement for Bentonite
Copper Addition
Manganese Addition
Molybdenite Addition

Dependent Responses

Crush Strength
Bulk Density
Surface Area
Porosity
Reactivity

A full parametric evaluation of all the variables at a variety of levels will result in an extremely large number of tests to be performed, which will be beyond the scope of the present program. Instead, we propose to investigate the primary variables initially using a 1/2 fractional factorial design. The levels to be examined for each primary variable are shown in Table 2 and the test matrix to be followed is shown in Table 3. For each sample formulation, about 20 pounds will be prepared and divided into subsamples for induration at different times and temperatures. Those samples that

are acceptable in terms of physical properties such as bulk density and crush strength will be used for evaluation of reactivity by single particle kinetic studies. These results will be used to select the final samples for bench-scale testing.

Table 2. Test Levels for Primary Variables

	Test Level	
	1	2
Iron Oxide Grade	Catalyst	Pigment
Zn/Fe Ratio	0.8	1.0
Bentonite Addition Level, %	3	10
Organic Binder Addition, %	0	2.0
Sorbent Shape	Pellets	Extrudes

Table 3. Statistical Screening Design Test Matrix

Run No.	Iron Oxide Grade ^a	Zn/Fe Ratio	Bentonite Addition Level, %	Organic Binder Addition, %	Sorbent Shape ^b
1	C	0.8	3	0.0	E
2	P	0.8	3	0.0	P
3	C	1.0	3	0.0	P
4	P	1.0	3	0.0	E
5	C	0.8	10	0.0	P
6	P	0.8	10	0.0	E
7	C	1.0	10	0.0	E
8	P	1.0	10	0.0	P
9	C	0.8	3	2.0	P
10	P	0.8	3	2.0	E
11	C	1.0	3	2.0	E
12	P	1.0	3	2.0	P
13	C	0.8	10	2.0	E
14	P	0.8	10	2.0	P
15	C	1.0	10	2.0	P
16	P	1.0	10	2.0	E

^a C = catalyst grade, P = pigment grade.

^b E = extrudes, P = pellets.

Figure 1 shows a schematic flow diagram for the tests to be performed. It is our estimate that upon completion of the entire program, about 50 samples will be prepared in Step 1, about 200 samples will be prepared and physically tested in Steps 2 and 3, about 50 samples will be subjected to single particle kinetic studies in Step 5, and about 15 to 30 samples will be tested in the bench-scale reactor in Step 6. These samples will represent a combination of samples examining primary and secondary variables. The base program calls for 15 samples to be tested, and Option 1 provides for testing of up to 15 additional samples. As mentioned earlier, we plan to test 2 samples prepared by UCI and AMAX as base case samples.

- Step 1. Prepare the 16 samples required for the screening design (about 20 pounds each).
- Step 2. Save 1/2 of each sample and divide the remaining half into 2 to 8 subsamples for induration at different times and temperatures (1,500 to 1,900°F, 15 minutes to 4 hours).
- Step 3. Measure bulk density and crush strength of the subsamples and select the best induration conditions for each sample.
- Step 4. Indurate under best conditions.
- Step 5. Perform surface area and porosity (as required) measurements to select samples for single particle kinetic studies to rank reactivity. Perform single particle kinetic studies.
- Step 6. Select up to 10 best samples for multi-cycle bench-scale testing.
- Step 7. Introduce secondary variables to the 5 best samples to examine the effects of these variables. Repeat Steps 1 through 6 to select 10 or more samples for multi-cycle bench-scale testing.
- Step 8. Perform bench-scale multi-cycle tests on high ranking samples to determine their reactivity and durability.
- Step 9. Evaluate the results and recommend additional tests as necessary.

Figure 1. Schematic flow chart for the proposed test program.

TASK 2. SORBENT PREPARATION AND CHARACTERIZATION

The following paragraphs briefly describe the apparatus and test procedures to be used in performing Task 2 — Sorbent Preparation and Characterization. In general, they will be similar to those used in our past work.² All of this work will be performed by AMAX in Golden, with the exception that porosity measurements on selected samples will be performed by an outside laboratory.

SORBENT PREPARATION

The starting material for all the sorbent samples will be commercially available chemicals in dry powder form. They will be weighed in desired proportions and mixed in a laboratory mix-muller. The powder will be hand fed with a scoop to a laboratory size (14-inch diameter) Dravo disc pelletizer, along with a fine spray of water. The disc angle and rotational speed will be adjusted to form the desired size (1/4-inch diameter) pellets. If necessary, screens will be used to remove oversize and undersize.

For those samples in which extrudes are to be tested, the powder mixture will be formed into a dough by adding the required amounts of water into a pug mill. A laboratory-size extruder will be used to prepare the extrudes of the desired size (3/16-inch diameter).

All sorbent formulations shown on the test matrix (Table 3) will be prepared in random order to minimize experimental bias.

Electric ovens and muffle furnaces will be used to dry and indurate the agglomerated sorbent samples. Samples will be taken before and after the drying and induration steps when desired to determine the moisture content of green agglomerates.

SORBENT CHARACTERIZATION

A graduated cylinder and weigh scale will be used to measure the bulk density of the indurated sorbent samples. Crush strength will be determined by using a Chatillon tension and compression tester. Attrition strength will be measured following ASTM procedures. Specific surface area of selected samples will be measured using a Quantachrome Quantasorb system. Porosity of selected samples will be measured using a mercury porosimeter.

Chemical analyses will be performed by standard chemical methods. The final samples selected for bench-scale testing will be examined by X-ray diffraction to estimate their zinc ferrite contents.

TASK 3. BENCH-SCALE TESTING

The reactivity and durability of the sorbents are strongly dependent upon the sulfidation and regeneration conditions used in testing them. However, the objective of the program is not to test this effect. Rather, it is the goal of the present program to perform a comparative evaluation of sorbent samples prepared under different conditions (Task 2) by subjecting them to a set of standard sulfidation and regeneration test conditions. These conditions have been selected based on past experience of METC and its contractors, including AMAX.

Since testing the sorbent in a bench-scale reactor for many cycles is expensive, it is planned to perform a preliminary evaluation of samples in single particle kinetic studies by the Department of Chemical Engineering at Louisiana State University (LSU) on a subcontract basis. Only the selected 15 to 30 samples will be investigated in multicycle bench-scale reactor tests. The apparatus and test procedures to be used in these two types of tests are briefly described below. Details can be found in the final reports submitted by AMAX and LSU to METC on their previous contracts.^{2,7}

SINGLE PARTICLE KINETIC STUDIES

These studies will be performed by LSU under a subcontract. It is envisioned to be a 15-month program in which about 50 sorbent samples will be subjected to one and a half cycle tests under standard conditions. There will be one complete cycle (sulfidation followed by regeneration), followed by a half-cycle (sulfidation only). The work will be part of an M. S. thesis, and theoretical interpretations developed for that purpose will become part of the results of the program.

Experimental Setup

A schematic diagram of the apparatus is shown in Figure 2. The key elements are a Cahn Model 2000 electrobalance, a temperature controlled furnace capable of isothermal operation or linear rates of temperature increase/decrease, and a manifold system to control feed rates of various gaseous components. The gas manifold system is shown in Figure 3. All gases (except steam) are obtained from high purity gas cylinders, and flow rates are controlled by regulating needle valves using calibrated rotameters. The desired amount of steam is introduced by metering distilled water into the gas mixture just before it enters the preheater.

Test Procedures

The sample (a single pellet or extrude) is heated to the test temperature under inert atmosphere and held there until a constant weight is obtained. Next, the simulated coal-gas (without any H_2S) is passed for 10 minutes. In some cases, weight loss is observed. At this point, H_2S is also introduced in the coal-gas. As the sorbent picks up H_2S , according to Reaction 1, its weight starts increasing. This weight gain is recorded as a function of time. The test is stopped when the rate of weight gain

Figure 2. Diagram of the apparatus for single particle kinetic studies.

Figure 3. Gas feed manifold.

becomes very slow, usually in 60 to 80 minutes. Both the final weight gain and the time taken to achieve this are used to determine the reactivity of the sorbent.

Next, the system is purged with an inert gas and its temperature adjusted to the desired regeneration temperature. At this point, a stream of oxygen, nitrogen, and steam mixture is passed to regenerate the sorbent sample. As the sulfur is oxidized to SO_2 , according to Reaction 2, the weight of the sample starts decreasing. When the sample attains its original weight, regeneration is stopped.

After purging the system with an inert gas, the next sulfidation cycle is started. The objective is to determine if a drastic change has occurred in the reactivity of the sorbent after just one cycle of testing.

Test Conditions

Since the purpose of single particle kinetic studies is to provide a quick and simple screening of various sorbent samples, it is important that the same test conditions be used for testing all the sorbents. Table 4 lists the conditions approved by METC for the test work.

Table 4. Recommended Test Conditions
for Single Particle Kinetic Studies

Sulfidation Gas Composition	
H ₂	10.6 volume percent
H ₂ O	25.3 volume percent
CO	16.3 volume percent
CO ₂	4.5 volume percent
H ₂ S	0.8 volume percent
N ₂	42.5 volume percent
Regeneration Gas Composition	
Oxygen	4 mole percent
Nitrogen	66 mole percent
Steam	30 mole percent
Sulfidation Temperature	550°C
Regeneration Temperature	700°C

Specifying these conditions does not preclude the possibility that LSU may perform additional tests under different conditions to enhance the theoretical understanding of the desulfurization and regeneration processes.

The sulfidation and regeneration time will be such that the reactions are essentially complete.

BENCH-SCALE TESTS

As mentioned earlier, a selected number of sorbents will be tested in the bench-scale reactor. A total of 15 samples are to be tested in the base program. It is proposed to test the base case sorbent T-2465 in the first test series. In the second test series, we plan to test AMAX sorbent 1094-63, which was produced in a 1-cubic foot quantity under the last project but was not tested.

Apparatus and Instruments

The test apparatus used during the past work will also be used in the present program with some minor modifications. Figure 4 shows the schematic diagram. The system consists of a packed-bed reactor made of a 2-inch I. D. by 36-inch long 446 stainless steel tube. The sorbent bed (about 18 inches) rests on about a 1/4-inch layer of alumina chips, which in turn rests on a perforated plate at the bottom of the reactor. During the sulfidation cycle, simulated coal-gas enters the bottom of the reactor and clean (low sulfur) gas exits at the top of the reactor. During regeneration, oxidizing gas (a mixture of steam and air) enters the top of the reactor and SO₂-rich exit gas leaves at the bottom of the reactor. Additional air is introduced in an afterburner to insure that any H₂S or elemental sulfur formed during regeneration is converted to SO₂.

A gas mixing manifold, M, is used to prepare the desired dry gas composition. Individual gases from cylinders are metered through needle valves and rotameters using a setup similar to that shown in Figure 3. From the manifold, the gas passes into an electric preheater. Water is added to the preheater at a specified rate to attain the desired steam content in the simulated coal-gas. Just before the gas enters the reactor, H₂S is introduced from a cylinder at a controlled rate to obtain the desired H₂S concentration.

Exit gases from either sulfidation or regeneration cycles are passed into a caustic scrubber before they are vented to the atmosphere. The apparatus is housed in a well ventilated laboratory with gas cylinders outside the building. Alarms for H₂S, SO₂, and CO are installed near the apparatus for proper safety of the workers.

Figure 4. Schematic diagram of bench-scale test apparatus.

The reactor is enclosed in a three-zone split-tube vertical furnace. A temperature controller is used to maintain the desired temperature in the reactor during sulfidation. Although Figure 4 shows six thermocouples for measuring temperature at six locations in the bed, the setup has been changed so that only three thermocouples will be used to measure the temperature at the top, middle, and bottom of the bed, respectively. The objective of this modification is to reduce the size of the thermowell, which was too large for a 2-inch diameter reactor and might have created some gas channeling. The thermocouples are hooked to a temperature recorder for permanent recording of temperatures during sulfidation and regeneration cycles. The exothermic nature of the regeneration reaction results in temperature rises that have been best controlled by selecting the appropriate regeneration gas composition.

The reactor operates at pressures only slightly above the atmospheric pressure. A differential pressure gauge is used to measure the pressure drop across the bed. A dramatic increase in the pressure drop would indicate severe sintering of the bed. This has generally not happened. A quartz-wool filter is used in the gas sample lines going to the gas chromatograph to remove any dust from the gas.

A gas chromatograph is used to measure the H_2S and SO_2 concentrations in the dry gas at room temperature during the sulfidation and regeneration cycles. The gas chromatograph is also used to monitor the dry gas composition of the simulated coal-gas. With proper calibration, the instrument is able to detect the H_2S concentration at about the 10 ppm level. For the present program, an H_2S concentration level of about 200 ppm is considered to be the breakthrough point. This represents over 98 percent sulfur removal when the feed gas contains about 1 percent H_2S . During the early parts of the sulfidation tests, and particularly during the early test series, dredger tubes are used to confirm the very low H_2S concentration (a few ppm) in the exit gas.

Test Procedures

A new test series is started by charging 0.93 liter of sorbent into the reactor, which fills it up to about 18 inches high. The mass of this volume of sorbent is determined and recorded before it is charged into the reactor. To start a sulfidation cycle, all the furnace, preheater, controller, recorder, gas chromatograph switches are turned on. The sorbent bed is brought to the desired temperature (600°C in past work and 550°C in the present program) in an inert atmosphere.

When the temperature is stabilized, the flow of the simulated gas is started. This marks the zero time for the sulfidation cycle. Each rotameter is checked to make sure that it is maintaining the proper flow rate. The gas chromatograph is used to verify gas analysis. At this point, the H_2S concentration in the exit gas is generally nondetectable and is recorded as 0 ppm. The pressure drop across the bed is measured.

As the test progresses, the temperature, pressure drop, and flow rates are measured and maintained at their specified levels. With a good sorbent, the H_2S concentration in the exit gas stays at an undetectable level for a few hours. Then it gradually rises to the 200 ppm level, which is considered the breakthrough point. At this point, the water and gas flow is stopped, except for nitrogen. This marks the end of the sulfidation cycle.

Test procedures for the regeneration cycle are similar. The furnace temperature is brought to 650°C under the flow of nitrogen. The preheaters are activated and set at a temperature of about 500°C . The gas chromatograph is programmed with the date and time. When the temperature is stable, the nitrogen flow is stopped and the flow of air and water is started at the specified rates. This marks the beginning of the regeneration cycle. As the regeneration front moves to the middle of the reactor with the highly sulfided sorbent present there, the temperature rises but the rise is generally limited to about 800°C . In this test program, regeneration temperatures will be maintained between 700 and 750°C .

Temperature, pressure drop across the bed, and gas flow rates are monitored throughout the test. Gas samples from the exit stream are analyzed by the gas chromatograph at about 10-minute intervals. When the SO_2 concentration falls below 0.5 percent, the regeneration cycle is considered complete. The flow of air and water is stopped and the flow of inert gas (nitrogen) is started.

Sulfidation and regeneration cycles are alternated following the procedures described above. It is planned to run the tests during the day shift only. In general, this would mean one day for sulfidation and one day for regeneration to complete one cycle. The sorbent bed would be maintained at temperature under a small flow of nitrogen during the night. It is planned to complete 10 cycles on each sorbent. This would mean that the sorbent has to be left in the reactor over the weekend. In this case, the temperature and nitrogen flow will be maintained.

During the 10th sulfidation cycle, sulfidation will be continued beyond breakthrough to the near saturation point when the H_2S concentration in the exit gas approaches the H_2S concentration in the inlet gas. This gives a more realistic idea of the reactivity of the sorbent to be expected in a commercial reactor. The end of this cycle will mark the end of the particular test series. After cooling the furnace, the reactor will be removed and opened, and the sorbent bed gently removed in a manner that will permit taking samples from the top, middle, and bottom of the reactor. After any required maintenance, the setup will be ready for the next test series.

Test Conditions

The goal of the present program is to develop a sorbent with enhanced reactivity and durability. To achieve this goal, sorbents prepared under different conditions (in Task 2) have to be tested under the same conditions. We realize that these conditions affect the reactivity and durability of the sorbent and should, therefore, be maintained within a specified range.

Based on past experience and knowledge of potential commercial processes that would include demonstration of hot gas clean-up in an integrated gasification combined cycle (IGCC), the test conditions approved by METC are presented in Table 5. If during the course of the program it is felt necessary to change some of these conditions, the COTR will be consulted and his approval obtained before making the change.

Table 5. Planned Test Conditions for Bench-Scale Tests

Bed Height	18 inches
Bed Volume	0.93 liter

Sulfidation Cycle

Temperature	550°C (1,022°F)
Gas Flow Rate	2,000 bed volumes per hour based on standard conditions of 60°F and 14.7 psia.
Gas Composition	
CO	16.3 volume percent
CO ₂	4.5 volume percent
H ₂	10.6 volume percent
H ₂ O	25.3 volume percent
H ₂ S	0.8 volume percent
N ₂	42.5 volume percent

Regeneration Cycle

Temperature	Preheater at 500°C, bed start at 650°C. Temperature 700 to 750°C.
Gas Flow Rate	1,500 bed volume per hour based on STP. Adjust down- ward to maintain temperature within the range.
Gas Composition	20 percent air, 80 percent steam (mole percent).
Afterburner Air Flow	2 liters (STP) per minute.

TASK 4. BENCH-SCALE TEST ANALYSIS

The goal of this task is to analyze and present the results in a manner that would permit comparative evaluation of durability and reactivity of various sorbents tested in the program. This will be done by collecting certain data during the actual bench-scale tests, as well as by analyzing sorbent samples collected after completion of a test series.

DATA ACQUISITION AND ANALYSIS

The following information will be recorded during each sulfidation cycle:

- Gas preheat temperature.
- Bed temperature as a function of thermocouple location.
- Pressure drop across the bed.
- Gas flow rate.
- Inlet gas composition.
- H_2S concentration in the exit gas as a function of time.
- Time to reach breakthrough or saturation.

The following information will be recorded during each regeneration cycle:

- Gas preheat temperature.
- Bed temperature as a function of thermocouple location and time.
- Pressure drop across the bed.
- Gas flow rate.
- SO_2 concentration in the exit gas as a function of time.
- Time required for regeneration.

Concentration of H_2S and cumulative sulfur loading will be recorded with elapsed time for each sulfidation cycle. Cumulative sulfur loading is calculated by a computer program based on sulfur input and output rates. These rates in turn are calculated from the actual gas flow rate and H_2S analysis in the feed and exit gas. From these data, and knowing the mass of the sorbent in the bed, sulfur sorption capacity of the sorbent (in terms of weight percent) will be calculated for each cycle.

A comparison of these sulfur sorption capacities at breakthrough during the 10 cycles of testing will be a good indicator of how the reactivity is maintained in multicycle tests for any given sorbent. A comparison with the results from other test series will help in determining which sorbent is more reactive.

PHYSICAL ANALYSES

At the end of each test series, samples of the sorbent collected from the top, middle, and bottom of the bed will be blended into one sample and used for determination of the following parameters:

- Disintegration of the sorbent, as measured by percent of minus 8-mesh material present in the sample.
- Shrinkage of the sorbent, as measured by its diameter and/or length before and after testing.
- Crush strength of the sorbent before and after testing.
- Attrition strength of the sorbent before and after testing.
- Specific surface area of the sorbent before and after testing.
- Porosity (mercury) of selected samples before and after testing.

CHEMICAL AND MINERALOGICAL ANALYSES

The three samples collected from the top, middle, and bottom of the reactor from each test series (last cycle, to near saturation) will be analyzed for sulfur, zinc, and iron using standard analytical methods. Sulfur analyses will give a good indication about the reactivity of the sorbent. Zinc and iron analyses will tell if any zinc migration has taken place. This has been of some concern in the past.

Samples of the regenerated sorbent may be removed from the reactor and analyzed for zinc, iron, and sulfur in some cases if it is thought that this information will be helpful in understanding the chemistry of the process.

The sorbent considered best will be analyzed for all its constituents before and after testing to determine if any significant change has taken place.

Optical microscopic, X-ray diffraction, and electron microprobe analyses will be used as appropriate to examine the surface or interior of fresh, partly sulfided, totally sulfided, partly regenerated, and totally regenerated samples from selected test series. This information has been very valuable in past work. The roles of modifiers and binders will probably be explained and understood better by performing these studies.

REFERENCES

1. Grindley, T. and Steinfeld, G., "Zinc Ferrite Hydrogen Sulfide Absorbent" in Proceedings of the Third Annual Contractors Meeting on Contaminant Control in Hot Coal Derived Gas Streams, K. E. Markel (Editor), DOE/METC/84-6(CONF-8305112) (DE 84000216), Morgantown Energy Technology Center, Morgantown, West Virginia, 1983, pp. 145-171.
2. Jha, M. C., Hepworth, M. T., and Baltich, L. K., "Enhanced Sorbent Durability for Hot Coal Gas Desulfurization", Final Report submitted to Morgantown Energy Technology Center for work performed under Contract DE-AC21-84MC21168, AMAX Extractive Research and Development Center, Golden, Colorado, March 1986.
3. Swalin, R. A., Thermodynamics of Solids, John Wiley and Sons, New York, 1962, pp. 306-312.
4. Rao, Y. K., "Catalysis in Extractive Metallurgy", Journal of Metals, July 1983, pp. 46-50.
5. Westmoreland, P. R. and Harrison, D. P., "Evaluation of Candidate Solids for High Temperature Desulfurization of Low Btu Gases", Environmental Science & Technology, Volume 10, No. 7, July 1976, pp. 659-661.
6. Olsson, R. G. and Turkdogan, E. T., "Desulfurization of Hot Reducing Gas", U. S. Patent 4,180,549, December 25, 1979.
7. Focht, G. D., Sa, L. N., Ranade, P. V., and Harrison, D. P., "Structural Property Changes in Metal Oxide Hot Coal Gas Desulfurization Sorbents", Final Report submitted to Morgantown Energy Technology Center for work performed under Contract DE-AC21-84MC21166, Louisiana State University, Baton Rouge, Louisiana, July 1986.

AMAX Extractive Research and
Development Center
5950 McIntyre Street
Golden, CO 80403 7499
303 279 7636

February 12, 1987

U. S. Department of Energy
Morgantown Energy Technology Center
P. O. Box 880
3610 Collins Ferry Road
Morgantown, WV 26507-0880

RECEIVED AND PROCESSED
2/17/87
Date
REPORTS RECEIPT

Attention: Mr. Suresh C. Jain

Dear Mr. Jain:

Re: Monthly Status Report for January 1987 for the Project "Enhanced Durability and Reactivity for Zinc Ferrite Desulfurization Sorbent", Contract No. DE-AC21-86MC23172

Attached please find the January 1987 Monthly Status Report for the above mentioned project. Three copies of this report are also being sent to the Contractor Reports Receipt Coordinator, M/S I05 (T-44), at METC. If you have any questions or comments, please feel free to call me at (303) 279-7636.

Sincerely yours,

A handwritten signature in cursive script, appearing to read "Mahesh C. Jha".

Mahesh C. Jha, Manager
Mineral & Energy Research

MCJ:wlk
Enclosure

cc: Contractor Reports Receipt Coordinator, M/S I05 (T-44), METC (3)
A. K. Bhasin
L. K. Baltich

END

**DATE
FILMED
9/01/92**