247
3/17/68

14. 1932

HEDL-TME 77-27

UC-79b

MASTER

HIGH-TEMPERATURE THERMODYNAMIC PROPERTIES OF SODIUM

Hanford Engineering Development Laboratory

HANFORD ENGINEERING DEVELOPMENT LABORATORY

Operated by Westinghouse Hanford Company

A Subsidiary of Westinghouse Electric Corporation

Prepared for the U.S. Department of Energy

under Contract No. EY-76-C-14-2170

P.O. Box 1970 Richland, WA 99352

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

DISCLAIMER

Portions of this document may be illegible in electronic image products. Images are produced from the best available original document.

NOTICE

This report was prepared as an account of work sponsored by the United States Government. Neither the United States nor the U.S. DOE, nor any of their employees, nor any of their contractors, subcontractors, or their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness or usefulness of any information, apparatus, product or process disclosed, or represents that its use would not infringe privately owned rights.

Printed in the United States of America
Available from
National Technical Information Service
U.S. Department of Commerce
5285 Port Royal Road
Springfield, Virginia 22161
Price: Printed Copy \$6.00 Microfiche \$2.25

HIGH-TEMPERATURE THERMODYNAMIC PROPERTIES OF SODIUM

Hanford Engineering Development Laboratory

**A. PADILLA, JR.
FEBRUARY 1978**

NOTICE

This report was prepared as an account of work sponsored by the United States Government. Neither the United States nor the United States Department of Energy, nor any of their employees, nor any of their contractors, subcontractors, or their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness or usefulness of any information, apparatus, product or process disclosed, or represents that its use would not infringe privately owned rights.

HANFORD ENGINEERING DEVELOPMENT LABORATORY
Operated by Westinghouse Hanford Company
A Subsidiary of Westinghouse Electric Corporation
Prepared for the U.S. Department of Energy
under Contract No. EY-76-C-14-2170

7

.

.

.

HIGH-TEMPERATURE THERMODYNAMIC PROPERTIES
OF SODIUM

A. Padilla, Jr.

ABSTRACT

The set of high-temperature thermodynamic properties for sodium in the two-phase and subcooled-liquid regions which was previously recommended^{2,3} has been modified to incorporate recent experimental data. In particular, replacement of the previously estimated critical constants with experimentally-determined values has resulted in substantial differences in the region of the critical point.

The following thermodynamic properties were determined: pressure, density, enthalpy, entropy, internal energy, compressibility (adiabatic and isothermal), thermal expansion coefficient, thermal pressure coefficient, and specific heat (constant-pressure and constant-volume). These properties were determined for the saturated liquid, saturated vapor, subcooled liquid, and superheated vapor. The superheated vapor properties are limited to low pressures and more work is required to extend them to higher pressures. The supercritical region was not investigated.

1

2

3

4

CONTENTS

	<u>Page</u>
ABSTRACT	iii
FIGURES AND TABLES	vii
NOMENCLATURE	ix
1.0 INTRODUCTION	1
2.0 SATURATED LIQUID AND VAPOR PROPERTIES	2
2.1 Critical Constants	2
2.2 Vapor Pressure	3
2.3 Enthalpy	4
2.4 Heat of Vaporization	6
2.5 Density	9
2.6 Internal Energy	11
2.7 Entropy	11
2.8 Liquid Compressibility	13
2.9 Liquid Thermal Expansion Coefficient	14
2.10 Liquid Thermal Pressure Coefficient	17
2.11 Liquid Specific Heat	17
2.12 Vapor Thermal Pressure Coefficient	18
2.13 Vapor Thermal Expansion Coefficient	20
2.14 Vapor Specific Heat	20
2.15 Vapor Compressibility	21
3.0 SUBCOOLED-LIQUID PROPERTIES	21
3.1 Thermal Pressure Coefficient	21
3.2 Pressure	21

CONTENTS (Cont'd)

	<u>Page</u>
3.3 Thermal Expansion Coefficient	22
3.4 Specific Heat	22
3.5 Compressibility	24
3.6 Enthalpy	24
3.7 Internal Energy	25
3.8 Entropy	25
4.0 SUPERHEATED-VAPOR PROPERTIES	25
4.1 Thermal Pressure Coefficient	25
4.2 Specific Heat	27
4.3 Thermal Expansion Coefficient	29
4.4 Compressibility	29
4.5 Enthalpy	29
4.6 Internal Energy	29
4.7 Entropy	29
5.0 SUMMARY	30
6.0 REFERENCES	31
APPENDIXES	
A. TABULATION OF SATURATED SODIUM LIQUID PROPERTIES	A-1
B. TABULATION OF SATURATED SODIUM VAPOR PROPERTIES	B-1
C. TABULATION OF SUBCOOLED-LIQUID SODIUM PROPERTIES	C-1
D. TABULATION OF SUPERHEATED-VAPOR SODIUM PROPERTIES	D-1

FIGURES

	<u>Page</u>
1. Vapor Pressure of Sodium	5
2. Temperature Derivative of Liquid Enthalpy	7
3. Heat of Vaporization of Sodium	10
4. Properties of Saturated Sodium	12
5. Correlation of Adiabatic Compressibility for Saturated Sodium Liquid	15
6. Properties of Saturated Sodium Liquid	16
7. Thermal Pressure Coefficient for Saturated Sodium	19
8. Properties of Subcooled Sodium Liquid	23
9. Thermal Pressure Coefficient for Sodium Vapor	26
10. Properties of Superheated Sodium Vapor	28

TABLES

	<u>Page</u>
1. Critical Constants of Sodium	3
2. Constants in Empirical Equation for Heat of Vaporization	9
3. Constants in Empirical Equation for Saturated Liquid Density	11

-

+

-

+

NOMENCLATURE

<u>SYMBOL</u>	<u>DEFINITION</u>
a	Constant in Eq. 20 for equilateral hyperbola
b	Constant in Eq. 20 for equilateral hyperbola
B_S	Adiabatic bulk modulus, MPa
B	Reduced adiabatic bulk modulus
C_o	Sonic velocity, m/sec
C_p	Specific heat at constant pressure, kJ/kg-°K
C_{sat}	Specific heat along the saturated liquid curve, kJ/kg-°K
C_v	Specific heat at constant volume, kJ/kg-°K
H	Enthalpy, kJ/kg
ΔH_{vap}	Enthalpy change due to vaporization, kJ/kg
P	Pressure, MPa
R	Gas constant, 8.314×10^{-6} MPa-m ³ /mole-°K
S	Entropy, kJ/kg-°K
t	Temperature, °F or °C
T	Absolute temperature, °R or °K
U	Internal energy, kJ/kg
V	Specific volume, m ³ /kg
α_p	Thermal expansion coefficient, °K ⁻¹
α_{sat}	Thermal expansion along the saturated liquid curve, °K ⁻¹
β_S	Adiabatic compressibility, MPa ⁻¹
β_T	Isothermal compressibility, MPa ⁻¹
γ_{sat}	Slope of vapor-pressure curve, dP_{sat}/dT_{sat} , MPa/°K
γ_V	Thermal pressure coefficient, MPa/°K
ρ	Density, kg/m ³
θ	Fractional liquid range between melting point and critical point
<u>SUBSCRIPTS</u>	
c	Critical point
liq	Liquid
mp	Melting point
T	Temperature T
sat	Saturation condition
vap	Vapor

HIGH-TEMPERATURE THERMODYNAMIC PROPERTIES OF SODIUM

1.0 INTRODUCTION

In the analysis of hypothetical accidents in sodium-cooled nuclear reactors, high-temperature sodium properties beyond the range of the available experimental data are often required. The work of Golden and Tokar⁽¹⁾ adequately covered the low-temperature region up to 1644°K (2500°F), but the analysis of thermal interactions between molten fuel and sodium coolant often required much higher temperatures. Padilla^(2,3) extrapolated the thermodynamic properties of sodium in the two-phase and subcooled-liquid regions from 1644°K to the estimated critical point.

Alderson⁽⁴⁾ extended the work of Padilla by completing the specification of saturated vapor properties (mechanical and thermal coefficients) and extending the predictions to the superheated vapor and supercritical regions. Breton⁽⁵⁾ also determined sodium properties over the entire fluid range, assuming the same critical constants. Both Alderson and Breton assumed that the thermal pressure coefficient approach, used as the equation-of-state for the subcooled-liquid region, would also apply to the superheated-vapor region. Barnes^(6,7) used statistical atom theory to develop sodium properties over the entire thermodynamic range.

The high-temperature properties which are based on extrapolations to the critical point have been rendered obsolete by the availability of new experimental data. In particular, Bhise and Bonilla⁽⁸⁾ have recently measured the critical point of sodium which is substantially different from the estimate used by Padilla, Alderson, and Breton.

The purpose of this report is to describe the incorporation of these recent experimental data into the previous prediction of high-temperature thermodynamic properties of sodium by this author. In addition to the new experimentally-determined critical point, the high-temperature vapor pressure of Bhise and Bonilla⁽⁸⁾ and the liquid enthalpy data of Fredrickson and

Chasanov⁽⁹⁾ have also been incorporated. The previous properties have been extended by completing the specification of saturated vapor properties and by extending the prediction into the superheated vapor region. However, the supercritical region above the critical isotherm was not investigated.

The approach used in the present study is to directly utilize correlations derived from the original experimental investigations whenever possible. These original correlations have been used at the expense of creating minor discontinuities in some properties even though empirical correlations could have been used to avoid these discontinuities. The intent is to make the experimental data base more visible and to facilitate the incorporation of new data when they become available.

2.0 SATURATED LIQUID AND VAPOR PROPERTIES

2.1 Critical Constants

The critical constants are very important in the prediction of the high-temperature saturated liquid and vapor properties because many of the empirical relationships use dimensionless ratios based on the critical point.

Table 1 compares the critical constants which have been recommended by various experimental and analytical investigators. Bhise and Bonilla⁽⁸⁾ directly measured the critical pressure and used this pressure along with their vapor pressure data to estimate the critical temperature. The critical density was estimated analytically using low-temperature liquid density data.⁽¹⁰⁾ The critical constants of Barnes and DeVault were determined from their statistical atom theory.⁽⁷⁾ Prior to the experimental determination of Bhise and Bonilla, Gabelnick⁽¹¹⁾ had estimated the critical point by using the experimental data of Bonilla and coworkers for cesium, rubidium, and potassium and extrapolating to sodium on the basis of atomic number. Miller, Cohen, and Dickerman⁽¹²⁾ estimated the critical constants of several alkali metals by assuming a corresponding states relationship with cesium, for which experimental data closer to the critical point were available at that time. The critical temperature proposed by Dillon et al.⁽¹³⁾ is remarkably close to that recommended by Bhise and Bonilla, but Dillon's work was not

seriously considered, probably because of the large discrepancy with other investigators. The analytical estimates of Grosse⁽¹⁴⁾ and Morris⁽¹⁵⁾ are examples of other early predictions.

Table 1
Critical Constants of Sodium

	T_c (°K)	P_c (MPa)	ρ_c (10 ⁻³ kg/m ³)	Z_c ($P_c/\rho_c RT_c$)
Bhise & Bonilla	2503	25.6	.2134	.13
Barnes & DeVault	2500-2525	29.0	.10	.32
Gabelnick	2406	19.5	.137	.16
Miller, Cohen, & Dickerman	2733	41.4	.1818	.23
Dillon	2573	35.5	.198	.19
Grosse	2780	49.6	.180	.27
Morris	2800	51.7	.153	.33

In the present study, the experimentally-based critical constants of Bhise and Bonilla have replaced the previously-used analytical estimate of Miller, Cohen, and Dickerman.

2.2 Vapor Pressure

In the previous study, the vapor pressure equations recommended by Golden and Tokar were used for temperatures up to 1644°K (2500°F). For temperatures below 1144°K (1600°F), they recommended the equation of Ditchburn and Gilmour:⁽¹⁶⁾

$$\log_{10} P_{\text{sat}} (\text{atm}) = 6.4818 - \frac{10020.6}{T_{\text{sat}} (^{\circ}\text{R})} - 0.5 \log_{10} T_{\text{sat}} (^{\circ}\text{R}) \quad (1)$$

In SI units, Equation (1) becomes:

$$P_{\text{sat}} (\text{MPa}) = 2.26041 \times 10^6 \exp(-12818.5/T_{\text{sat}}) / T_{\text{sat}}^{0.5} \quad (2)$$

For temperatures from 1144°K to 1644°K (2500°F), they recommended the equation of Stone et al.:⁽¹⁷⁾

$$\log_{10} P_{\text{sat}} (\text{atm}) = 6.83770 - \frac{9980.94}{T_{\text{sat}} (^{\circ}\text{R})} - 0.61344 \log_{10} T_{\text{sat}} (^{\circ}\text{R}) \quad (3)$$

In SI units, Equation (3) becomes:

$$P_{\text{sat}}(\text{MPa}) = 4.86207 \times 10^5 \exp(-12767.8/T_{\text{sat}}) / T_{\text{sat}}^{0.61344} \quad (4)$$

Since there were no experimental data beyond 1644°K, an equation of the same form as Equation (4) was used to extrapolate the vapor pressures to the estimated critical point.

In addition to measuring the critical pressure, Bhise and Bonilla also obtained vapor pressure measurements from 1255°K up to almost the critical point and recommended the following equation (SI units):

$$P_{\text{sat}}(\text{MPa}) = 4.12679 \times 10^3 \exp(-11936.2/T_{\text{sat}}) / T_{\text{sat}}^{0.039972} \quad (5)$$

They used Equation (5) to calculate the critical temperature using the measured critical pressure of 25.64 MPa.

Figure 1 compares Equations (4) and (5) and shows that the vapor pressures obtained from the equation of Stone et al. are slightly higher (~2%) than those obtained from the equation of Bhise and Bonilla in the region where they overlap (1255°K to 1644°K). Although it would be desirable to fit a single equation to the combined data, it was decided to use Equations (4) and (5) directly and accept the 2% discontinuity in vapor pressure at the transition point. To minimize the impact of this discontinuity, the transition point was chosen to be 1255°K instead of 1644°K. Therefore, the present study uses the equation of Ditchburn and Gilmour below 1144°K, the equation of Stone et al. from 1144°K up to 1255°K, and the equation of Bhise and Bonilla from 1255°K to the critical point.

2.3 Enthalpy

For the liquid enthalpy up to 1644°K (2500°F), Golden and Tokar recommended the following equation:

$$H_{\text{liq}}(\text{Btu/lb}_m) = 0.389352T - 0.552955 \times 10^{-4}T^2 + 0.113726 \times 10^{-7}T^3 - 29.023 \quad (6)$$

where the temperature T is in degrees Rankine, and the enthalpy is calculated relative to the standard state at 0°K. Equation (6) was originally derived by Ginnings, Douglas, and Ball⁽¹⁸⁾ from their experimental measurements between 273°K and 1173°K, but was extended to 1644°K by Stone, et al.⁽¹⁷⁾

HEDL 7703-106.3

FIGURE 1. Vapor Pressure of Sodium

In SI units, Equation (6) becomes:

$$H_{liq}(\text{J/kg}) = 1629.05T - 0.416441T^2 + 1.54169 \times 10^{-4}T^3 - 67462.3 \quad (7)$$

More recently, Fredrickson and Chasanov⁽⁹⁾ experimentally measured the enthalpy of liquid sodium (above the reference temperature of 298.15°K) from 554°K to 1505°K and recommended the following equation (SI units):

$$H_{liq}(\text{J/mole}) = 19.3483T + 3.53315 \times 10^{-3}T^2 - 2.47879 \times 10^6/T + 3062.40 \quad (8)$$

The temperature derivative of the saturated liquid enthalpy (dH_{liq}/dT) is frequently used for the constant-pressure specific heat for conditions far from the critical point. Figure 2 shows that the agreement in the temperature derivatives for Equations (7) and (8) is very good over the temperature range where the experimental measurements overlap (554°K to 1173°K). The agreement deteriorates at low temperatures near the melting point (outside the experimental range for Equation (8)), and at higher temperatures (outside the experimental range for Equation (7)).

Therefore, it was decided to use Equation (7) from the melting point up to 740°K, where the temperature derivatives become equal, and Equation (8) from 740°K to 1644°K. The reference condition was chosen as the standard state at 0°K, and the constant term in Equation (8) was adjusted to give the same value for liquid enthalpy at 740°K as that determined from Equation (7).

To determine the vapor enthalpies up to 1644°K, the heat of vaporization, which will be discussed in the next section, is added to the liquid enthalpies. Beyond 1644°K, the average enthalpy (one-half of the liquid plus vapor) is linearly extrapolated to the new critical temperature of 2503°K. The liquid and vapor enthalpies between 1644°K and the critical temperature of 2503°K are obtained by subtracting and adding one-half of the heat of vaporization from the average enthalpy respectively. Figure 4A compares the saturated liquid and vapor enthalpies calculated in the present study with those of the previous study.

2.4 Heat of Vaporization

Up to 1644°K, Golden and Tokar recommended the quasi-chemical approach to calculate the heat of vaporization. This approach starts with the

FIGURE 2. Temperature Derivative of Liquid Enthalpy

HEDL 7709-20.1

assumption that the sodium vapor is composed of monomer (Na), dimer (Na_2), and tetramer (Na_4), and that these are all perfect gases. The equilibrium constants for the chemical reactions to form the dimer and tetramer are a function of temperature and are calculated from P-V-T data. These equilibrium constants are then used to determine the composition and mean molecular weight of the vapor at a particular temperature and pressure. The mole fractions of the individual components are used with their respective heats of formation from the saturated liquid to calculate the heat of vaporization.

Golden and Tokar also calculated the heat of vaporization using the virial approach. This approach consisted of calculating the sodium vapor density from the virial equation-of-state and using the Clapeyron equation to determine the heat of vaporization. They compared the values computed by both the virial and quasi-chemical approaches with the experimental data of Achener and Jouthas⁽¹⁹⁾ and based their recommendation of the quasi-chemical approach on this comparison.

Golden and Tokar indicated that their choice was based on the available experimental data and that future experimental data might dictate a different approach. For example, extension of the measurements for saturated-liquid specific heat to higher temperatures would probably strengthen the choice of a liquid-base calculation, such as the quasi-chemical approach, whereas precise P-V-T measurements might lead to the choice of a gas-base calculation, such as the virial approach.

They developed a computer program to calculate the thermodynamic properties of sodium up to 1644°K based on the quasi-chemical approach. For the vapor pressure, their computer program used the equation of Ditchburn and Gilmour (Equation (1)) for temperatures below 1144°K and the equation of Stone et al. (Equation (3)) from 1144°K to 1644°K. For the enthalpy of the saturated liquid, it used the equation of Ginnings, Douglas, and Ball (Equation (6)). This computer program was modified to account for the additional correlations for vapor pressure and liquid enthalpy which were recommended in the previous two sections.

Between 1644°K and the critical point, an empirical equation originally suggested by Miller, Cohen, and Dickerman⁽¹²⁾ is used to calculate the heat

of vaporization:

$$\frac{\Delta H_{\text{vap}}}{RT_c} = A_H (1 - T/T_c)^{B_H} \quad (9)$$

The constants A_H and B_H were evaluated by insuring continuity in the saturated liquid enthalpy and its temperature derivative at 1644°K. Table 2 compares the values of A_H and B_H with those which have been used previously. Figure 3 compares the heats of vaporization calculated in the present study with those of the previous study.

Table 2
Constants in Empirical Equation for Heat of Vaporization

	Miller	Previous Study	Present Study
A_H	4.83	5.050	5.172
B_H	0.377	0.4262	0.3056

2.5 Density

For the saturated liquid up to 1644°K, Golden and Tokar recommended the equation proposed by Stone et al.:⁽¹⁷⁾

$$\rho_{\text{liq}} (\text{lb}_m/\text{ft}^3) = 59.566 - 7.9504 \times 10^{-3} t - 0.2872 \times 10^{-6} t^2 + 0.06035 \times 10^{-9} t^3 \quad (10)$$

where the temperature t is in degrees Fahrenheit. In SI units, Equation (10) becomes:

$$\rho_{\text{liq}} (\text{kg}/\text{m}^3) = 16.01846 [59.566 - 7.9504 \times 10^{-3} (1.8T - 459.67) - 0.2872 \times 10^{-6} (1.8T - 459.67)^2 + 0.06035 \times 10^{-9} (1.8T - 459.67)^3] \quad (11)$$

Between 1644°K and the critical point, an empirical equation originally suggested by Miller, Cohen, and Dickerman⁽¹²⁾ is used:

$$\frac{\rho_{\text{liq}}}{\rho_c} = 1 + A_L (1 - T/T_c)^{B_L} \quad (12)$$

The constants A_L and B_L were evaluated by insuring continuity in the saturated liquid density and its temperature derivative at 1644°K. Table 3 compares the values for A_L and B_L with those which have been used previously.

FIGURE 3. Heat of Vaporization of Sodium

Table 3
Constants in Empirical Equation for Saturated Liquid Density

	<u>Miller</u>	<u>Previous Study</u>	<u>Present Study</u>
A_L	4.097	4.163	3.270
B_L	0.682	0.5885	0.5002

For the saturated vapor up to 1644°K, the modified computer program (discussed in the previous section) which implements the quasi-chemical approach is used. Compared to the previous values, the new saturated vapor densities are about 2% lower from 1255°K to 1644°K because of the incorporation of the Bhise-Bonilla vapor pressure equation. Between 1644°K and the critical point, the saturated vapor densities are calculated using the Clapeyron equation:

$$\gamma_{\text{sat}} = \left(\frac{dP}{dT} \right)_{\text{sat}} = \frac{\Delta H_{\text{vap}}}{T \left(\frac{1}{\rho_{\text{vap}}} - \frac{1}{\rho_{\text{liq}}} \right)} \quad (13)$$

The temperature derivative of the vapor pressure, γ_{sat} , is obtained by differentiating Equation (5). The heat of vaporization and the saturated liquid density are calculated from Equations (9) and (12), respectively.

Figure 4B compares the saturated liquid and vapor densities calculated in the present study with those of the previous study.

2.6 Internal Energy

The internal energy for both the saturated liquid and vapor is calculated using the standard thermodynamic relationship:

$$U = H - PV \quad (14)$$

where V is the specific volume ($1/\rho$).

2.7 Entropy

The entropy of the saturated liquid is obtained from the second law of thermodynamics:

FIGURE 4. Properties of Saturated Sodium

$$dS_{liq} = \frac{dQ}{T} = \frac{C_{sat}}{T} dT \quad (15)$$

where C_{sat} is the specific heat along the saturated liquid curve and is given by:

$$C_{sat} = \left(\frac{dH_{liq}}{dT} \right)_{sat} - \frac{\gamma_{sat}}{\rho_{liq}} \quad (16)$$

Integrating Equation (15) from the melting point gives:

$$S_{liq} = S_{liq}(m.p.) + \int_{m.p.}^T \frac{C_{sat}}{T} dT \quad (17)$$

The entropy of the saturated vapor is obtained by adding the entropy of vaporization to the liquid entropy:

$$S_{vap} = S_{liq} + \Delta S_{vap} = S_{liq} + \frac{\Delta H_{vap}}{T} \quad (18)$$

Figure 4C compares the values of the saturated liquid and vapor entropies calculated in the present study with those obtained in the previous study.

2.8 Liquid Compressibility

The adiabatic compressibility for saturated sodium liquid can be calculated from the sonic velocity, C_o , by the equation:

$$\beta_s = \frac{1}{\rho C_o^2} \quad (19)$$

The sonic velocity data of Leibowitz et al.⁽²⁰⁾ for temperatures up to 1273°K and of Chasanov et al.⁽²¹⁾ for temperatures between 1273°K and 1773°K, and Equation (10) for the saturated liquid density, were used to calculate values for β_s up to 1773°K. To extrapolate β_s to the critical point, the calculated values of β_s were empirically correlated using the equation for an equilateral hyperbola, as suggested by Grosse:⁽²²⁾

$$(B' + b)(\theta + b) = a, \quad (20)$$

where B' is the reduced adiabatic bulk modulus:

$$B' = \frac{B_{s,T}}{B_{s,mp}} = \frac{\beta_{s,mp}}{\beta_{s,T}} \quad ; \quad (21)$$

and θ is the fractional liquid range between the melting point and the critical point:

$$\theta = \frac{T - T_{mp}}{T_c - T_{mp}} \quad (22)$$

Fourteen equally-spaced points between the melting point and 1773°K were used to obtain a least-squares fit to Equation (20). Figure 5 shows that the agreement between the empirical correlation and the experimental data is not as good in the present study, and the standard deviation for the 14 data points is 36% higher than in the previous study. However, the maximum individual deviations for the 14 points are only about 2%.

The isothermal compressibility for saturated sodium liquid is calculated using the equation recommended by Rowlinson⁽²³⁾:

$$\beta_T = \frac{\beta_s C_{sat} + TV\alpha_{sat} (\alpha_{sat} + \beta_s \gamma_{sat})}{C_{sat} - TV\gamma_{sat} (\alpha_{sat} + \beta_s \gamma_{sat})} \quad (23)$$

where α_{sat} is the thermal expansion along the saturated liquid curve:

$$\alpha_{sat} = -\frac{1}{\rho} \left(\frac{d\rho}{dT} \right)_{sat} \quad (24)$$

The values for α_{sat} are calculated from Equation (10) for temperatures up to 1644°K and from Equation (12) for temperatures between 1644°K and the critical point.

Figure 6A compares the values for β_s and β_T calculated in this study with those obtained in the previous study.

2.9 Liquid Thermal Expansion Coefficient

The thermal expansion coefficient for the saturated liquid is calculated from the equation:

$$\alpha_p = \alpha_{sat} + \beta_T \gamma_{sat} \quad (25)$$

HEDL 7704-011.12

FIGURE 5. Correlation of Adiabatic Compressibility for Saturated Sodium Liquid

A. COMPRESSIBILITY

B. THERMAL EXPANSION COEFFICIENT

C. THERMAL PRESSURE COEFFICIENT

D. SPECIFIC HEAT

FIGURE 6. Properties of Saturated Sodium Liquid

All the quantities on the right side of Equation (25) were discussed above. Figure 6B compares the thermal expansion coefficients which have been determined in this study with those obtained in the previous study.

2.10 Liquid Thermal Pressure Coefficient

The thermal pressure coefficient for the saturated liquid is calculated from the equation:

$$\gamma_v = \frac{\alpha_p}{\beta_T} \quad (26)$$

At the critical point, γ_v becomes equal to γ_{sat} , the temperature derivative of the vapor pressure.

Figure 6C compares the thermal pressure coefficients which have been determined in this study with those obtained in the previous study. In the previous study, the linear behavior of the γ_v curve near the critical point was not realistic because the shape of the P-V-T surface dictates a vertical slope at the critical point. Therefore, the properties calculated in the previous study were recommended for use only up to within 100°K of the critical point. However, the values for α_p , β_T , and γ_v calculated in the present study exhibit reasonable behavior all the way to critical point. Therefore, no such limitations on the present set of high-temperature properties are required.

2.11 Liquid Specific Heat

The constant-pressure specific heat for the saturated liquid is calculated from the equation:

$$C_p = C_{sat} + TV\alpha_p\gamma_{sat} \quad (27)$$

where all of the quantities on the right side were discussed previously. The constant-volume specific heat for the saturated liquid is calculated from C_p by the equation:

$$C_v = C_p \frac{\beta_s}{\beta_T} \quad (28)$$

Figure 6D compares the specific heats determined in this study with those obtained in the previous study.

2.12 Vapor Thermal Pressure Coefficient

In the previous study, the mechanical (α_p , β_s , β_T , and γ_v) and thermal (C_p and C_v) coefficients for the saturated vapor were not determined. In the case of the saturated liquid, an empirical equation was used to extrapolate the adiabatic compressibility β_s to the critical point, thus making it possible to calculate the rest of the mechanical and thermal coefficients using standard thermodynamic relationships. For the saturated vapor, the thermal pressure coefficient was chosen as the starting point.

The thermal pressure coefficient for saturated sodium vapor up to 1644°K can be calculated using the quasi-chemical or virial approach. For the quasi-chemical approach, the thermal pressure coefficient is evaluated numerically using the modified computer program discussed earlier:

$$\gamma_v = \left(\frac{\partial P}{\partial T} \right)_v \sim P(T_{\text{sat}} + 1, V_{\text{sat}}) - P(T_{\text{sat}}, V_{\text{sat}}) \quad (29)$$

For a virial equation of the form:

$$\frac{PV}{RT} = 1 + \frac{B}{V} + \frac{C}{V^2} + \frac{D}{V^3} \quad , \quad (30)$$

the thermal pressure coefficient is obtained by evaluating the required temperature derivative at constant volume:

$$\gamma_v = \left(\frac{\partial P}{\partial T} \right)_v = \frac{P}{T} + \frac{RT}{V} \left(\frac{1}{V} \frac{\partial B}{\partial T} + \frac{1}{V^2} \frac{\partial C}{\partial T} + \frac{1}{V^3} \frac{\partial D}{\partial T} \right) \quad (31)$$

Up to 1644°K, the values for the thermal pressure coefficient calculated by both the quasi-chemical approach and the virial equation agree very well. However, when these two approaches are used to calculate γ_v beyond 1644°K, the predicted values rapidly diverge, as shown in Figure 7, and neither method correctly extrapolates to γ_{sat} , the known value at the critical point. Also, the thermal pressure coefficient would be expected to be continuous when passing from the vapor to the liquid, thus requiring a vertical slope at the critical point.

HEDL 7703-106.5

FIGURE 7. Thermal Pressure Coefficient for Saturated Sodium

In order to obtain the desired behavior near the critical point, the following equation is used:

$$\gamma_v = \frac{c_1}{V - c_2} \quad (32)$$

When the two constants, c_1 and c_2 , are evaluated empirically by using the values of γ_v at 1644°K and the critical point, Equation (32) appears to provide the expected behavior near the critical point as shown in Fig. 7. Therefore, the quasi-chemical approach is used to calculate γ_v up to 1644°K, and Equation (32) is used from 1644°K to the critical point.

2.13 Vapor Thermal Expansion Coefficient

The thermal expansion coefficient for the saturated vapor is evaluated numerically up to 1644°K using the quasi-chemical approach:

$$\alpha_p = \frac{1}{V} \left(\frac{\partial V}{\partial T} \right)_p \sim \frac{V(T_{\text{sat}} + 1, P_{\text{sat}}) - V(T_{\text{sat}}, P_{\text{sat}})}{V(T_{\text{sat}}, P_{\text{sat}})} \quad (33)$$

From 1644°K to the critical point, the thermal expansion coefficient is calculated from the thermal pressure coefficient using the equation:

$$\alpha_p = \frac{\alpha_{\text{sat}}}{1 - \frac{\gamma_{\text{sat}}}{\gamma_v}} \quad (34)$$

2.14 Vapor Specific Heat

The constant-pressure and constant-volume specific heats for the saturated vapor are evaluated numerically up to 1644°K using the quasi-chemical approach:

$$c_p = \left(\frac{\partial H}{\partial T} \right)_p \sim H(T_{\text{sat}} + 1, P_{\text{sat}}) - H(T_{\text{sat}}, P_{\text{sat}}) \quad (35)$$

$$c_v = \left(\frac{\partial U}{\partial T} \right)_v \sim U(T_{\text{sat}} + 1, v_{\text{sat}}) - U(T_{\text{sat}}, v_{\text{sat}}) \quad (36)$$

Between 1644°K and the critical point, the constant-pressure and constant-volume specific heats are calculated using the following equations:

$$C_p = C_{sat} + TV\alpha_p\gamma_{sat} \quad (37)$$

$$C_V = C_p - TV\alpha_p\gamma_V \quad (38)$$

2.15 Vapor Compressibility

The isothermal and adiabatic compressibilities for the saturated vapor are calculated using the following equations:

$$\beta_T = \frac{\alpha_p}{\gamma_V} \quad (39)$$

$$\beta_s = \beta_T \left(\frac{C_V}{C_p} \right) \quad (40)$$

3.0 SUBCOOLED-LIQUID PROPERTIES

3.1 Thermal Pressure Coefficient

Rowlinson⁽²³⁾ pointed out that the variation of the thermal pressure coefficient with temperature along the isochores (constant-volume paths) is always small. If it is assumed that the variation of the thermal pressure coefficient along the isochores is negligible, then γ_V becomes a function of specific volume only; i.e.,

$$\gamma_V = \left(\frac{\partial P}{\partial T} \right)_V = f(V) \quad (41)$$

To determine γ_V in the subcooled-liquid region, it is necessary only to know the specific volume and the value of γ_V for the saturated liquid at the same specific volume.

3.2 Pressure

The pressure in the subcooled-liquid region is obtained by integrating Equation (41) along a constant-volume path, where γ_V remains constant, starting from a point on the saturated liquid curve:

$$P(V=V_{\text{sat}}, T) = P_{\text{sat}}(V_{\text{sat}}) + \gamma_V(T - T_{\text{sat}}) \quad (42)$$

This equation is the equation-of-state for the subcooled liquid region.

3.3 Thermal Expansion Coefficient

Since the thermal expansion coefficient is defined by:

$$\alpha_p = \frac{1}{V} \left(\frac{\partial V}{\partial T} \right)_p = - \frac{1}{\rho} \left(\frac{\partial \rho}{\partial T} \right)_p, \quad (43)$$

use of Equation (42) to evaluate $(\partial T / \partial \rho)_p$ results in the following relationship:

$$\frac{1}{\alpha_p} = \frac{1}{(\alpha_p)_{\text{sat}}} + \frac{\rho(P - P_{\text{sat}})}{\gamma_V^2} \frac{d\gamma_V}{d\rho} \quad (44)$$

The two points to be used in Equation (44) are $(T, P, V=V_{\text{sat}})$ and $(T_{\text{sat}}, P_{\text{sat}}, V_{\text{sat}})$ which have the same specific volume and, therefore, the same thermal pressure coefficient. The density derivative of γ_V , $d\gamma_V/d\rho$, is evaluated along the saturated liquid curve.

Figure 8A compares the thermal expansion coefficients which are calculated in this study with those obtained in the previous study.

3.4 Specific Heat

Since γ_V is assumed to be a function of specific volume only,

$$\left(\frac{\partial \gamma_V}{\partial T} \right)_V = 0 \quad (45)$$

Using Equation (45), it can be shown that the constant-volume specific heat for the subcooled liquid is a function of temperature only:

$$\left(\frac{\partial C_V}{\partial V} \right)_T = T \left(\frac{\partial^2 P}{\partial T^2} \right)_V = T \left(\frac{\partial \gamma_V}{\partial T} \right)_V = 0 \quad (46)$$

To determine C_V , it is necessary only to know the value for the saturated liquid at the same temperature.

HEDL 7703-106.8

FIGURE 8. Properties of Subcooled Sodium Liquid

The constant-pressure specific heat for the subcooled liquid is calculated from the equation:

$$C_p = C_v + TV\alpha_p\gamma_v \quad (47)$$

Figure 8B compares the constant-pressure specific heats which have been calculated in this study with those obtained in the previous study.

3.5 Compressibility

The isothermal compressibility for the subcooled liquid is calculated from the equation:

$$\beta_T = \frac{\alpha_p}{\gamma_v} \quad (48)$$

An alternate method of calculating β_T is based on its definition:

$$\beta_T = -\frac{1}{V} \left(\frac{\partial V}{\partial P} \right)_T = \frac{1}{\rho} \left(\frac{\partial \rho}{\partial P} \right)_T \quad (49)$$

Use of Equation (42) to evaluate $(\partial P / \partial \rho)_T$ results in the following relationship:

$$\frac{1}{\beta_T} = \frac{1}{(\beta_T)_{sat}} + \rho(T - T_{sat}) \frac{d\gamma_v}{d\rho} \quad (50)$$

Figure 8C compares the isothermal compressibilities which are calculated in this study with those obtained in the previous study.

The adiabatic compressibility for the subcooled liquid is determined from the equation:

$$\beta_s = \beta_T - \frac{TV\alpha_p^2}{C_p} \quad (51)$$

3.6 Enthalpy

The effect of pressure on enthalpy in the subcooled-liquid region is given by:

$$\left(\frac{\partial H}{\partial P} \right)_T = V - T \left(\frac{\partial V}{\partial T} \right)_P = V(1 - T\alpha_p) \quad (52)$$

Using the values of α_p calculated with Equation (44), Equation (52) is integrated along a constant-temperature path starting from a point on the saturated liquid curve:

$$H = H_{\text{sat}} + \int_{p_{\text{sat}}}^p V(1 - T\alpha_p)dp \quad (53)$$

3.7 Internal Energy

The internal energy of the subcooled liquid is calculated using Equation (14).

3.8 Entropy

The effect of pressure on entropy in the subcooled-liquid region is given by:

$$\left(\frac{\partial S}{\partial P}\right)_T = - \left(\frac{\partial V}{\partial T}\right)_P = - V\alpha_p \quad (54)$$

Using the values of α_p calculated with Equation (44), Equation (54) is integrated along a constant-temperature path starting from a point on the saturated liquid curve:

$$S = S_{\text{sat}} - \int_{p_{\text{sat}}}^p V\alpha_p dT \quad (55)$$

4.0 SUPERHEATED-VAPOR REGION

4.1 Thermal Pressure Coefficient

Both Alderson⁽⁴⁾ and Breton⁽⁵⁾ assumed that the same equation-of-state for the subcooled-liquid region, Equation (42), could be applied to the superheated-vapor region. However, unlike the subcooled-liquid region, other equations-of-state exist for the superheated-vapor region which can be utilized to test the assumption that the thermal pressure coefficient is a function of specific volume only.

Figure 9 shows the variation of the thermal pressure coefficient in the superheated-vapor region along several isochores (constant-volume paths)

FIGURE 9. Thermal Pressure Coefficient for Sodium Vapor

as predicted by the quasi-chemical approach and the virial equation-of-state using Equations (29) and (31), respectively. If the thermal pressure coefficient were a function of specific volume only, all of the curves in the superheated-vapor region would be horizontal. In spite of the fact that the thermal pressure coefficients are not constant along the isochores, the thermal pressure coefficient approach was investigated as a possible equation-of-state for the superheated vapor region along with the quasi-chemical approach and the virial equation-of-state.

4.2 Specific Heat

For the superheated vapor region, the values for the constant-volume and constant-pressure specific heats would be expected to approach the ideal gas values at low pressures.

Figure 10A compares the constant-volume specific heats calculated using the quasi-chemical approach and the thermal pressure coefficient approach. As expected, the values predicted by the quasi-chemical method asymptotically approach the ideal gas value of $\frac{3}{2} R$ as the pressure is decreased. However, the values predicted by the thermal pressure coefficient approach are a function of temperature only. This result was previously derived in Equation (46) and is a consequence of the assumption that the thermal pressure coefficient is a function of specific volume only. Therefore, the thermal pressure coefficient approach can be eliminated as a reasonable equation-of-state for the superheated vapor region because of the unreasonable values predicted for the constant-volume specific heat.

It was shown earlier that differences in the values for the thermal pressure coefficient of sodium vapor predicted by the quasi-chemical approach and the virial equation-of-state were relatively small for pressures up to the saturation value corresponding to about 1700°K (see Figure 9). However, differences between the quasi-chemical and virial approaches are magnified when vapor specific heats are calculated because of the increased sensitivity of these derivatives to error. Figure 10B compares the constant-pressure specific heats for the quasi-chemical approach and the virial equation-of-state. For both approaches, the low-pressure values for the superheated vapor show the correct behavior and asymptotically

C. THERMAL EXPANSION COEFFICIENT

FIGURE 10. Properties of Superheated Sodium Vapor

approach the ideal gas value of $\frac{5}{2} R$. However, there are substantial differences in the values for the saturated vapor. For the same reasons as given by Golden and Tokar, the quasi-chemical approach was chosen over the virial equation as the equation-of-state for the superheated-vapor region.

4.3 Thermal Expansion Coefficient

The thermal expansion coefficient for the superheated vapor is evaluated numerically using the quasi-chemical approach:

$$\alpha_p = \frac{1}{V} \left(\frac{\partial V}{\partial T} \right)_p \sim \frac{V(T+1, P) - V(T, P)}{V(T, P)} \quad (56)$$

Figure 10C shows the thermal expansion coefficients calculated using Equation (56). As expected, the low-pressure values asymptotically approach the ideal gas values of $1/T$.

4.4 Compressibility

The isothermal and adiabatic compressibilities for the superheated vapor are calculated using Equations (39) and (40), respectively.

4.5 Enthalpy

The enthalpy for the superheated vapor is calculated from the quasi-chemical approach using the equation of Ewing et al.:⁽²⁴⁾

$$H(T, P) = H^0(T) + X_2 \Delta H_2^0 + X_4 \Delta H_4^0 \quad (57)$$

where the superscript 0 refers to the standard state, X_2 and X_4 are the weight fractions of dimer and tetramer, and H_2^0 and H_4^0 are the heats of formation of the dimer and tetramer.

4.6 Internal Energy

The internal energy for the superheated vapor is calculated using Equation (14).

4.7 Entropy

The entropy for the superheated vapor is calculated from the quasi-chemical approach using the equation of Ewing et al.:⁽²⁴⁾

$$\begin{aligned}
S(T, P) = S^0(T) + \frac{X_2 H_2^0}{T} + \frac{X_4 H_2^0}{T} - \frac{R}{M} \ln P + \frac{RX_2}{2M_1} \ln K_2 \\
+ \frac{RX_4}{4M_1} \ln K_4 - \frac{R(N_1 \ln N_1 + N_2 \ln N_2 + N_4 \ln N_4)}{\bar{M}}
\end{aligned} \quad (58)$$

where N_1 , N_2 , and N_4 are the mole fractions of monomer, dimer, and tetramer, and K_2 and K_4 are the equilibrium constants for the chemical reactions to form the dimer and tetramer.

5.0 SUMMARY

The set of high temperature thermodynamic properties of sodium previously recommended for sodium-cooled nuclear reactor safety analysis has been modified to incorporate recent experimental data for liquid enthalpy, vapor pressure, and the critical point. A new set of properties for the saturated liquid, saturated vapor, and subcooled liquid up to the critical isotherm have been developed. A set of properties for the superheated vapor has been developed for temperatures up to 1644°K.

To develop a consistent set of superheated vapor properties for higher temperatures, it will be necessary to determine the equilibrium constants for the chemical reactions to form the dimer, tetramer, and other polyatomic species.

These properties should constantly be reviewed to determine the desirability of incorporating new experimental data whenever they become available. For example, the availability of new P-V-T data may make it desirable to use the virial approach instead of the quasi-chemical approach which is currently used. Also, the availability of experiment data in the subcooled liquid region would make it possible to check the validity of the assumed equation-of-state (the thermal pressure coefficient approach) for that region.

6.0 REFERENCES

1. G. H. Golden and J. V. Tokar, Thermophysical Properties of Sodium, ANL-7323, Argonne National Laboratory, Argonne, Illinois, 1967.
2. A. Padilla, Jr., "High-Temperature Properties of Sodium for Safety Studies of Liquid-Metal Fast Breeder Reactors," Nucl. Sci. Eng., 55, p. 452-461, 1974.
3. A. Padilla, Jr., High-Temperature Thermodynamic Properties of Sodium, ANL-8095, Argonne National Laboratory, Argonne, Illinois, 1974.
4. M. A. H. G. Alderson, "An Equation of State for Use with Sodium - Part I - Theory and Computer Program," SRD-R-50 (Pt. 1), United Kingdom Atomic Energy Authority, Wigshaw Lane, Culcheth Warrington, 1975.
5. J. P. Breton, "A Simple and Consistent Equation of State for Sodium in the Single Phase and Two Phase Regions," PNC N251 76012, Proceedings of the Third Specialist Meeting on Sodium/Fuel Interaction in Fast Reactors, Tokyo, Japan, March 22-26, 1976.
6. J. F. Barnes, "An Equation of State for Sodium over an Extended Temperature and Density Range," in Thermodynamics of Nuclear Materials 1974, Vol. 1 (published by the International Atomic Energy Agency, Vienna, Austria, 1975), pp. 327-339.
7. J. F. Barnes and G. P. DeVault, "Equations of State for LMFBR Materials," Proceedings of the International Meeting on Fast Reactor Safety and Related Physics, CONF-761002, Vol. IV, Chicago, Illinois, October 5-8, 1976.
8. V. S. Bhise and C. F. Bonilla, "The Experimental Vapor Pressure and Critical Point of Sodium," Proceedings of the International Conference on Liquid Metal Technology in Energy Production, CONF-760503-P2, Champion, Pennsylvania, May 3-6, 1976.
9. D. R. Fredrickson and M. G. Chasanov, "The Enthalpy of Liquid Sodium to 1505 K by Drop Calorimetry," J. Chem. Thermodynamics 1974, 6, pp. 629-633.
10. V. S. Bhise and C. F. Bonilla, "The Critical and High Temperature Equilibrium Phase Densities of Sodium and Potassium," Proceedings of the Seventh Symposium on Thermophysical Properties, National Bureau of Standards, Gaithersburg, Maryland, May 10-12, 1977.
11. "Chemical Engineering Division Annual Report for Reactor Safety and Physical Properties Studies Annual Report - July 1973-June 1974," ANL-8120, Argonne National Laboratory, Argonne, Illinois, pp. 12-59.

12. D. Miller, A. B. Cohen, and C. E. Dickerman, "Estimation of Vapor and Liquid Density and Heat of Vaporization of the Alkali Metals to the Critical Point," Proceedings of the International Conference on the Safety of Fast Breeder Reactors, Aix-en-Provence, France, September 19-22, 1967.
13. I. G. Dillon, "Measurement of Densities and Estimation of Critical Properties of the Alkali Metals," J. Chem. Phys., 44, 4229-4328, 1966.
14. A. V. Grosse, "The Liquid Range of Metals and Some of the Physical Properties at High Temperatures," in USAEC File No. NP-10895, 1960.
15. E. Morris, "An Application of the Theory of Corresponding States to the Prediction of the Critical Constants of Metals," British Report AWRE-O-67/64, 1964.
16. R. W. Ditchburn and J. C. Gilmour, "The Vapor Pressures of Monatomic Vapors," Rev. Mod. Phys., 13, 310, 1941.
17. J. P. Stone, et al., High-Temperature Properties of Sodium, NRL-6241, Naval Research Laboratory, 1965.
18. D. C. Ginnings, T. B. Douglas, and A. F. Ball, "Heat Capacity of Sodium Between 0 and 900°C, the Triple Point and Heat of Fusion," J. Res. NBS, 45, 23-33, 1950.
19. P. V. Achener and J. T. Jouthas, The Latent Heat of Vaporization and Vapor Pressure of Sodium, AGN-8191, Vol. 1, Aerojet General Corporation, 1966.
20. L. Leibowitz, et al., "Speed of Sound in Liquid Sodium to 1000°C," J. Appl. Phys., 42, 2135-2137, 1971.
21. M. G. Chasanov, et al., "Speed of Sound in Liquid Sodium from 1000° to 1500°C," J. Appl. Phys., 43, 745-749, 1972.
22. A. V. Grosse, "Simple Empirical Relationship Between the Compressibility of Ideal Liquids and Temperature Up to the Critical Point," Nature Physical Science, 232, 170, 1971.
23. J. S. Rowlinson, Liquids and Liquid Mixtures, 2nd Ed., Plenum Press, New York, 1969.
24. C. T. Ewing, et al., High-Temperature Properties of Potassium, NRL-6233, Naval Research Laboratory, 1965.

APPENDIX A

Tabulation of Saturated Sodium Liquid Properties

<u>Property</u>	<u>Symbol</u>	<u>Units</u>
Temperature	TSAT	K
Pressure	PSAT	MPa
Density	RHOL	g/cm ³
Enthalpy	HLIQ	J/g
Internal Energy	ELIQ	J/g
Entropy	SLIQ	J/g·K
Thermal-Expansion Coefficient	ALPHAP	K ⁻¹
Adiabatic Compressibility	BETAS	MPa ⁻¹
Isothermal Compressibility	BETAT	MPa ⁻¹
Thermal Pressure Coefficient	GAMMAV	MPa/K
Constant-Pressure Specific Heat	CP	J/g·K
Constant-Volume Specific Heat	CV	J/g·K

PROPERTIES OF SATURATED SODIUM LIQUID

TSAT (K)	PSAT (MPA)	RHOL (G/CC)	HLIQ (J/G)	LLIQ (J/G)	SLIQ (J/G-K)	ALPHAP (K-1)	BETAS (MPA-1)	BETAT (MPA-1)	GAMMAV (MPA/K)	CP (J/G-K)	CV (J/G-K)
380	.26303E-10	.92537	499.9	499.9	2.8533	.25146E-03	.17008E-03	.18891E-03	.13311E+01	1.3793	1.2419
390	.61660E-10	.92304	513.7	513.7	2.8890	.25237E-03	.17115E-03	.19072E-03	.13232E+01	1.3746	1.2335
400	.13847E-09	.92071	527.4	527.4	2.9238	.25328E-03	.17222E-03	.19256E-03	.13153E+01	1.3699	1.2252
410	.29885E-09	.91837	541.1	541.1	2.9575	.25419E-03	.17330E-03	.19443E-03	.13074E+01	1.3653	1.2170
420	.62169E-09	.91604	554.7	554.7	2.9904	.25510E-03	.17439E-03	.19632E-03	.12994E+01	1.3608	1.2088
430	.12492E-08	.91370	568.3	568.3	3.0224	.25602E-03	.17550E-03	.19824E-03	.12915E+01	1.3564	1.2008
440	.24316E-08	.91136	581.8	581.8	3.0535	.25694E-03	.17661E-03	.20018E-03	.12835E+01	1.3521	1.1929
450	.45939E-08	.90902	595.3	595.3	3.0838	.25786E-03	.17773E-03	.20215E-03	.12755E+01	1.3479	1.1851
460	.84400E-08	.90667	608.8	608.8	3.1134	.25878E-03	.17887E-03	.20415E-03	.12676E+01	1.3438	1.1774
470	.15107E-07	.90432	622.2	622.2	3.1423	.25970E-03	.18002E-03	.20618E-03	.12596E+01	1.3398	1.1698
480	.26385E-07	.90197	635.6	635.6	3.1704	.26063E-03	.18118E-03	.20824E-03	.12516E+01	1.3358	1.1622
490	.45037E-07	.89962	648.9	648.9	3.1979	.26155E-03	.18235E-03	.21032E-03	.12436E+01	1.3320	1.1548
500	.75234E-07	.89727	662.2	662.2	3.2248	.26248E-03	.18353E-03	.21243E-03	.12356E+01	1.3282	1.1475
510	.12315E-06	.89491	675.5	675.5	3.2511	.26341E-03	.18472E-03	.21457E-03	.12276E+01	1.3246	1.1403
520	.19775E-06	.89255	688.7	688.7	3.2768	.26434E-03	.18593E-03	.21674E-03	.12196E+01	1.3210	1.1332
530	.31188E-06	.89019	701.9	701.9	3.3019	.26528E-03	.18714E-03	.21894E-03	.12116E+01	1.3175	1.1262
540	.48355E-06	.88783	715.1	715.1	3.3265	.26621E-03	.18837E-03	.22117E-03	.12036E+01	1.3142	1.1193
550	.73773E-06	.88547	728.2	728.2	3.3506	.26715E-03	.18962E-03	.22343E-03	.11956E+01	1.3109	1.1125
560	.11085E-05	.88310	741.3	741.3	3.3742	.26809E-03	.19087E-03	.22572E-03	.11877E+01	1.3077	1.1058
570	.16417E-05	.88073	754.3	754.3	3.3973	.26903E-03	.19214E-03	.22805E-03	.11797E+01	1.3046	1.0992
580	.23983E-05	.87836	767.4	767.4	3.4199	.26997E-03	.19342E-03	.23040E-03	.11718E+01	1.3016	1.0927
590	.34584E-05	.87599	780.4	780.4	3.4422	.27091E-03	.19472E-03	.23278E-03	.11638E+01	1.2986	1.0863
600	.49259E-05	.87362	793.3	793.3	3.4640	.27186E-03	.19603E-03	.23520E-03	.11559E+01	1.2958	1.0800
610	.69343E-05	.87124	806.3	806.3	3.4854	.27281E-03	.19735E-03	.23765E-03	.11480E+01	1.2931	1.0738
620	.96532E-05	.86886	819.2	819.2	3.5064	.27376E-03	.19869E-03	.24013E-03	.11401E+01	1.2904	1.0677
630	.13296E-04	.86648	832.1	832.1	3.5270	.27471E-03	.20004E-03	.24264E-03	.11322E+01	1.2879	1.0618
640	.18129E-04	.86410	845.0	845.0	3.5473	.27566E-03	.20140E-03	.24519E-03	.11243E+01	1.2854	1.0559
650	.24481E-04	.86172	857.8	857.8	3.5672	.27662E-03	.20278E-03	.24777E-03	.11165E+01	1.2831	1.0501

PROPERTIES OF SATURATED SODIUM LIQUID

TSAT (K)	PSAT (MPA)	KHOL (G/CC)	HLIQ (J/G)	ELIQ (J/G)	SLIQ (J/G-K)	ALPHAP (K-1)	BETAS (MPA-1)	BETAT (MPA-1)	GAMMAV (MPA/K)	CP (J/G-K)	CV (J/G-K)
660	.32755E-04	.85933	870.6	870.6	3.5867	.27757E-03	.20418E-03	.25038E-03	.11086E+01	1.2608	1.0445
670	.43442E-04	.85695	883.4	883.4	3.6060	.27853E-03	.20559E-03	.25303E-03	.11008E+01	1.2786	1.0389
680	.57132E-04	.85456	896.2	896.2	3.6249	.27949E-03	.20701E-03	.25571E-03	.10930E+01	1.2765	1.0335
690	.74535E-04	.85217	909.0	909.0	3.6435	.28046E-03	.20845E-03	.25842E-03	.10853E+01	1.2746	1.0281
700	.96492E-04	.84978	921.7	921.7	3.6619	.28142E-03	.20991E-03	.26117E-03	.10775E+01	1.2727	1.0229
710	.12400E-03	.84739	934.4	934.4	3.6799	.28239E-03	.21139E-03	.26396E-03	.10698E+01	1.2708	1.0177
720	.15823E-03	.84499	947.1	947.1	3.6977	.28336E-03	.21288E-03	.26678E-03	.10621E+01	1.2691	1.0127
730	.20054E-03	.84260	959.8	959.8	3.7152	.28433E-03	.21438E-03	.26964E-03	.10545E+01	1.2675	1.0076
740	.25253E-03	.84020	972.5	972.5	3.7324	.28530E-03	.21591E-03	.27254E-03	.10468E+01	1.2659	1.0029
750	.31601E-03	.83780	985.1	985.1	3.7494	.28628E-03	.21745E-03	.27550E-03	.10391E+01	1.2638	.9975
760	.39309E-03	.83541	997.7	997.7	3.7661	.28725E-03	.21901E-03	.27850E-03	.10314E+01	1.2619	.9923
770	.48616E-03	.83301	1010.4	1010.3	3.7826	.28823E-03	.22058E-03	.28153E-03	.10238E+01	1.2601	.9873
780	.59796E-03	.83060	1022.9	1022.9	3.7988	.28922E-03	.22218E-03	.28459E-03	.10162E+01	1.2586	.9826
790	.73156E-03	.82820	1035.5	1035.5	3.8149	.29020E-03	.22379E-03	.28769E-03	.10087E+01	1.2572	.9779
800	.89044E-03	.82580	1048.1	1048.1	3.8307	.29118E-03	.22543E-03	.29083E-03	.10012E+01	1.2560	.9735
810	.10785E-02	.82339	1060.6	1060.6	3.8463	.29217E-03	.22708E-03	.29400E-03	.99379E+00	1.2549	.9693
820	.13001E-02	.82099	1073.2	1073.2	3.8617	.29316E-03	.22875E-03	.29721E-03	.98639E+00	1.2540	.9652
830	.15600E-02	.81858	1085.7	1085.7	3.8768	.29415E-03	.23044E-03	.30045E-03	.97904E+00	1.2532	.9612
840	.18637E-02	.81617	1098.3	1098.2	3.8918	.29515E-03	.23216E-03	.30373E-03	.97174E+00	1.2526	.9574
850	.22171E-02	.81376	1110.8	1110.8	3.9067	.29615E-03	.23389E-03	.30705E-03	.96447E+00	1.2521	.9537
860	.26266E-02	.81135	1123.3	1123.3	3.9213	.29714E-03	.23564E-03	.31041E-03	.95725E+00	1.2517	.9502
870	.30995E-02	.80894	1135.8	1135.8	3.9358	.29815E-03	.23742E-03	.31381E-03	.95008E+00	1.2514	.9468
880	.36435E-02	.80653	1148.3	1148.3	3.9501	.29915E-03	.23922E-03	.31725E-03	.94294E+00	1.2513	.9435
890	.42673E-02	.80411	1160.8	1160.8	3.9642	.30016E-03	.24104E-03	.32073E-03	.93585E+00	1.2512	.9403
900	.49799E-02	.80170	1173.3	1173.3	3.9782	.30117E-03	.24288E-03	.32425E-03	.92880E+00	1.2513	.9373
910	.57916E-02	.79929	1185.9	1185.9	3.9920	.30218E-03	.24474E-03	.32782E-03	.92179E+00	1.2514	.9343
920	.67130E-02	.79687	1198.4	1198.4	4.0057	.30319E-03	.24663E-03	.33142E-03	.91482E+00	1.2517	.9315
930	.77560E-02	.79445	1210.9	1210.9	4.0192	.30421E-03	.24855E-03	.33507E-03	.90789E+00	1.2520	.9287

PROPERTIES OF SATURATED SODIUM LIQUID

TSAT (K)	PSAT (MPA)	RMOL (G/CC)	HLIQ (J/G)	ELIQ (J/G)	SLIQ (J/G-K)	ALPHAP (K-1)	BETAS (MPA-1)	DETAT (MPA-1)	GAMMAV (MPA/K)	CP (J/G-K)	CV (J/G-K)
940	.89330E-02	.79204	1223.4	1223.4	4.0326	.30523E-03	.25048E-03	.33877E-03	.90100E+00	1.2524	.9261
950	.10257E-01	.78962	1236.0	1235.9	4.0459	.30625E-03	.25245E-03	.34250E-03	.89415E+00	1.2529	.9235
960	.11744E-01	.78720	1248.5	1248.5	4.0590	.30727E-03	.25443E-03	.34624E-03	.88733E+00	1.2535	.9210
970	.13407E-01	.78476	1261.0	1261.0	4.0720	.30830E-03	.25645E-03	.35012E-03	.88056E+00	1.2542	.9186
980	.15264E-01	.78236	1273.6	1273.6	4.0849	.30933E-03	.25849E-03	.35400E-03	.87382E+00	1.2549	.9163
990	.17332E-01	.77994	1286.1	1286.1	4.0976	.31037E-03	.26056E-03	.35793E-03	.86712E+00	1.2557	.9141
1000	.19629E-01	.77752	1298.7	1298.7	4.1102	.31140E-03	.26265E-03	.36190E-03	.86046E+00	1.2566	.9120
1010	.22175E-01	.77510	1311.3	1311.2	4.1227	.31244E-03	.26477E-03	.36593E-03	.85383E+00	1.2575	.9099
1020	.24989E-01	.77268	1323.8	1323.8	4.1351	.31349E-03	.26693E-03	.37001E-03	.84724E+00	1.2585	.9079
1030	.28095E-01	.77026	1336.4	1336.4	4.1474	.31453E-03	.26911E-03	.37414E-03	.84069E+00	1.2595	.9059
1040	.31514E-01	.76784	1349.0	1349.0	4.1596	.31558E-03	.27132E-03	.37832E-03	.83417E+00	1.2606	.9041
1050	.35270E-01	.76542	1361.7	1361.6	4.1717	.31664E-03	.27356E-03	.38256E-03	.82768E+00	1.2618	.9023
1060	.39388E-01	.76299	1374.3	1374.2	4.1836	.31770E-03	.27583E-03	.38685E-03	.82124E+00	1.2630	.9005
1070	.43894E-01	.76057	1386.9	1386.9	4.1955	.31876E-03	.27813E-03	.39120E-03	.81482E+00	1.2643	.8989
1080	.48816E-01	.75815	1399.6	1399.5	4.2072	.31982E-03	.28047E-03	.39560E-03	.80844E+00	1.2656	.8972
1090	.54181E-01	.75572	1412.2	1412.2	4.2189	.32089E-03	.28284E-03	.40007E-03	.80209E+00	1.2669	.8957
1100	.60020E-01	.75330	1424.9	1424.8	4.2305	.32196E-03	.28524E-03	.40459E-03	.79577E+00	1.2683	.8942
1110	.66363E-01	.75088	1437.6	1437.5	4.2420	.32304E-03	.28768E-03	.40917E-03	.78949E+00	1.2697	.8927
1120	.73241E-01	.74845	1450.3	1450.2	4.2534	.32412E-03	.29015E-03	.41382E-03	.78324E+00	1.2712	.8913
1130	.80689E-01	.74603	1463.1	1462.9	4.2647	.32521E-03	.29266E-03	.41853E-03	.77702E+00	1.2727	.8900
1140	.88739E-01	.74361	1475.8	1475.7	4.2759	.32629E-03	.29521E-03	.42330E-03	.77084E+00	1.2743	.8887
1150	.97176E-01	.74118	1488.6	1488.4	4.2870	.32738E-03	.29779E-03	.42813E-03	.76468E+00	1.2759	.8874
1160	.10637E+00	.73876	1501.3	1501.2	4.2981	.32848E-03	.30041E-03	.43303E-03	.75855E+00	1.2775	.8862
1170	.11625E+00	.73633	1514.1	1514.0	4.3090	.32958E-03	.30307E-03	.43801E-03	.75246E+00	1.2791	.8851
1180	.12685E+00	.73391	1526.9	1526.8	4.3199	.33069E-03	.30577E-03	.44305E-03	.74640E+00	1.2808	.8840
1190	.13820E+00	.73149	1539.6	1539.6	4.3307	.33180E-03	.30852E-03	.44816E-03	.74036E+00	1.2825	.8829
1200	.15036E+00	.72906	1552.6	1552.4	4.3415	.33292E-03	.31130E-03	.45335E-03	.73436E+00	1.2843	.8819
1210	.16334E+00	.72664	1565.5	1565.2	4.3521	.33404E-03	.31413E-03	.45861E-03	.72838E+00	1.2861	.8809

PROPERTIES OF SATURATED SODIUM LIQUID

TSAT (K)	PSAT (MPA)	HMOL (G/CC)	HLIQ (J/G)	ELIQ (J/G)	SLIQ (J/G-K)	ALPHAP (K-1)	BETAS (MPA-1)	BETAT (MPA-1)	GAMMAV (MPA/K)	CP (J/G-K)	CV (J/G-K)
1220	.17720E+00	.72422	1578.3	1578.1	4.3627	.33517E-03	.31700E-03	.46394E-03	.72244E+00	1.2879	.8800
1230	.19198E+00	.72180	1591.2	1591.0	4.3732	.33630E-03	.31992E-03	.46935E-03	.71652E+00	1.2897	.8791
1240	.20770E+00	.71937	1604.2	1603.9	4.3837	.33744E-03	.32288E-03	.47484E-03	.71063E+00	1.2916	.8782
1250	.22443E+00	.71695	1617.1	1616.8	4.3940	.33858E-03	.32589E-03	.48042E-03	.70477E+00	1.2934	.8774
1260	.23853E+00	.71453	1630.1	1629.7	4.4043	.33971E-03	.32895E-03	.48605E-03	.69893E+00	1.2954	.8767
1270	.25692E+00	.71211	1643.0	1642.7	4.4146	.34087E-03	.33205E-03	.49178E-03	.69312E+00	1.2973	.8759
1280	.27641E+00	.70969	1656.0	1655.6	4.4248	.34203E-03	.33521E-03	.49761E-03	.68734E+00	1.2993	.8752
1290	.29704E+00	.70727	1669.1	1668.6	4.4349	.34319E-03	.33842E-03	.50352E-03	.68159E+00	1.3012	.8746
1300	.31885E+00	.70485	1682.1	1681.6	4.4449	.34436E-03	.34169E-03	.50952E-03	.67586E+00	1.3032	.8740
1310	.34190E+00	.70243	1695.2	1694.7	4.4549	.34554E-03	.34501E-03	.51561E-03	.67017E+00	1.3052	.8734
1320	.36622E+00	.70001	1708.2	1707.7	4.4648	.34673E-03	.34838E-03	.52180E-03	.66449E+00	1.3073	.8728
1330	.39187E+00	.69760	1721.3	1720.8	4.4747	.34792E-03	.35182E-03	.52808E-03	.65884E+00	1.3093	.8723
1340	.41889E+00	.69518	1734.5	1733.9	4.4845	.34912E-03	.35531E-03	.53446E-03	.65322E+00	1.3114	.8716
1350	.44733E+00	.69276	1747.6	1747.0	4.4942	.35033E-03	.35886E-03	.54094E-03	.64762E+00	1.3135	.8714
1360	.47723E+00	.69035	1760.8	1760.1	4.5039	.35154E-03	.36247E-03	.54753E-03	.64205E+00	1.3156	.8709
1370	.50866E+00	.68793	1774.0	1773.2	4.5135	.35277E-03	.36615E-03	.55422E-03	.63650E+00	1.3177	.8706
1380	.54165E+00	.68552	1787.2	1786.4	4.5231	.35399E-03	.36990E-03	.56102E-03	.63098E+00	1.3199	.8702
1390	.57626E+00	.68310	1800.4	1799.6	4.5326	.35523E-03	.37371E-03	.56794E-03	.62548E+00	1.3220	.8699
1400	.61254E+00	.68069	1813.7	1812.8	4.5421	.35648E-03	.37759E-03	.57496E-03	.62000E+00	1.3242	.8696
1410	.65053E+00	.67828	1827.0	1826.0	4.5515	.35773E-03	.38154E-03	.58210E-03	.61455E+00	1.3264	.8694
1420	.69030E+00	.67587	1840.3	1839.2	4.5609	.35899E-03	.38556E-03	.58937E-03	.60912E+00	1.3286	.8692
1430	.73188E+00	.67346	1853.6	1852.5	4.5702	.36027E-03	.38966E-03	.59675E-03	.60371E+00	1.3308	.8690
1440	.77535E+00	.67105	1866.9	1865.8	4.5794	.36155E-03	.39384E-03	.60426E-03	.59833E+00	1.3330	.8688
1450	.82073E+00	.66864	1880.3	1879.1	4.5887	.36284E-03	.39809E-03	.61190E-03	.59297E+00	1.3353	.8687
1460	.86810E+00	.66624	1893.7	1892.4	4.5978	.36414E-03	.40243E-03	.61967E-03	.58763E+00	1.3375	.8686
1470	.91750E+00	.66383	1907.1	1905.7	4.6069	.36544E-03	.40685E-03	.62758E-03	.58231E+00	1.3398	.8686
1480	.96898E+00	.66143	1920.6	1919.1	4.6160	.36676E-03	.41136E-03	.63562E-03	.57701E+00	1.3421	.8686
1490	.10226E+01	.65902	1934.0	1932.5	4.6250	.36809E-03	.41595E-03	.64381E-03	.57174E+00	1.3444	.8686

PROPERTIES OF SATURATED SODIUM LIQUID

TSAT (K)	PSAT (MPA)	RHQL (G/CC)	HLIQ (J/G)	ELIQ (J/G)	SLIQ (J/G-K)	ALPHAP (K-1)	BETAS (MPA-1)	BETAT (MPA-1)	GAMMAV (MPA/K)	CP (J/G-K)	CV (J/G-K)
1500	.10784E+01	.65662	1947.5	1945.9	4.6340	.36943E-03	.42064E-03	.65215E-03	.56648E+00	1.3467	.8686
1510	.11365E+01	.65422	1961.1	1959.3	4.6429	.37078E-03	.42542E-03	.66064E-03	.56125E+00	1.3490	.8687
1520	.11968E+01	.65182	1974.6	1972.8	4.6518	.37214E-03	.43030E-03	.66928E-03	.55603E+00	1.3514	.8688
1530	.12595E+01	.64942	1988.2	1986.2	4.6606	.37351E-03	.43528E-03	.67808E-03	.55084E+00	1.3537	.8690
1540	.13246E+01	.64703	2001.8	1999.7	4.6694	.37490E-03	.44037E-03	.68705E-03	.54566E+00	1.3561	.8692
1550	.13922E+01	.64463	2015.4	2013.2	4.6781	.37629E-03	.44556E-03	.69618E-03	.54051E+00	1.3585	.8694
1560	.14622E+01	.64224	2029.0	2026.7	4.6868	.37770E-03	.45086E-03	.70549E-03	.53537E+00	1.3608	.8697
1570	.15349E+01	.63984	2042.7	2040.3	4.6955	.37912E-03	.45627E-03	.71498E-03	.53026E+00	1.3632	.8700
1580	.16101E+01	.63745	2056.4	2053.8	4.7041	.38055E-03	.46180E-03	.72465E-03	.52516E+00	1.3656	.8703
1590	.16881E+01	.63506	2070.1	2067.4	4.7127	.38200E-03	.46745E-03	.73450E-03	.52008E+00	1.3681	.8707
1600	.17687E+01	.63268	2083.8	2081.0	4.7212	.38346E-03	.47323E-03	.74456E-03	.51501E+00	1.3705	.8711
1610	.18521E+01	.63029	2097.6	2094.7	4.7297	.38493E-03	.47914E-03	.75481E-03	.50997E+00	1.3729	.8715
1620	.19384E+01	.62790	2111.4	2108.3	4.7382	.38642E-03	.48518E-03	.76527E-03	.50494E+00	1.3754	.8720
1630	.20275E+01	.62552	2125.2	2122.0	4.7466	.38792E-03	.49135E-03	.77595E-03	.49993E+00	1.3779	.8725
1640	.21196E+01	.62314	2139.1	2135.7	4.7550	.38944E-03	.49768E-03	.78684E-03	.49494E+00	1.3803	.8731
1650	.22146E+01	.62076	2152.9	2149.4	4.7633	.39244E-03	.50415E-03	.79985E-03	.49064E+00	1.3843	.8725
1660	.23127E+01	.61836	2166.9	2163.1	4.7716	.39660E-03	.51077E-03	.81465E-03	.48683E+00	1.3895	.8712
1670	.24139E+01	.61595	2180.8	2176.9	4.7799	.40086E-03	.51755E-03	.82990E-03	.48302E+00	1.3948	.8698
1680	.25182E+01	.61353	2194.9	2190.8	4.7882	.40522E-03	.52450E-03	.84562E-03	.47920E+00	1.4002	.8685
1690	.26257E+01	.61109	2208.4	2204.7	4.7965	.40969E-03	.53162E-03	.86182E-03	.47538E+00	1.4058	.8671
1700	.27364E+01	.60864	2223.1	2218.6	4.8047	.41427E-03	.53891E-03	.87853E-03	.47154E+00	1.4114	.8658
1710	.28504E+01	.60617	2237.3	2232.6	4.8129	.41896E-03	.54639E-03	.89577E-03	.46770E+00	1.4172	.8645
1720	.29678E+01	.60366	2251.5	2246.6	4.8211	.42376E-03	.55406E-03	.91357E-03	.46385E+00	1.4232	.8631
1730	.30886E+01	.60118	2265.9	2260.7	4.8293	.42868E-03	.56193E-03	.93194E-03	.45999E+00	1.4292	.8618
1740	.32128E+01	.59866	2280.2	2274.9	4.8375	.43373E-03	.57000E-03	.95091E-03	.45613E+00	1.4355	.8605
1750	.33404E+01	.59613	2294.7	2289.1	4.8456	.43892E-03	.57829E-03	.97052E-03	.45225E+00	1.4419	.8591
1760	.34716E+01	.59358	2309.2	2303.3	4.8538	.44423E-03	.58680E-03	.99078E-03	.44836E+00	1.4484	.8578
1770	.36064E+01	.59101	2323.7	2317.6	4.8619	.44969E-03	.59555E-03	.10117E-02	.44447E+00	1.4551	.8565

PROPERTIES OF SATURATED SODIUM LIQUID

TSAT (K)	PSAT (MPA)	RHOL (G/CC)	HLIQ (J/G)	ELIQ (J/G)	SLIQ (J/G-K)	ALPHAP (K-1)	BETAS (MPA-1)	BETAT (MPA-1)	GAMMAV (MPA/K)	CP (J/G-K)	CV (J/G-K)
1700	.37448E+01	.58843	2338.4	2332.0	4.8700	.45529E-03	.6045JE-03	.10334E-02	.44056E+00	1.4620	.8553
1750	.38869E+01	.5858J	2353.1	2346.4	4.8701	.46104E-03	.61377E-03	.10559E-02	.43665E+00	1.4691	.8540
1800	.40327E+01	.58321	2367.8	2360.9	4.8862	.46696E-03	.62327E-03	.10791E-02	.43273E+00	1.4764	.8527
1810	.41823E+01	.58057	2382.7	2375.5	4.8943	.47304E-03	.63305E-03	.11032E-02	.42879E+00	1.4838	.8515
1820	.43356E+01	.57791	2397.6	2390.1	4.9023	.47929E-03	.64311E-03	.11281E-02	.42485E+00	1.4915	.8503
1830	.44928E+01	.5752J	2412.6	2404.8	4.9104	.48572E-03	.65347E-03	.11540E-02	.42089E+00	1.4994	.8490
1840	.46539E+01	.57253	2427.6	2419.5	4.9184	.49233E-03	.66414E-03	.11809E-02	.41692E+00	1.5075	.8479
1850	.48190E+01	.56981	2442.8	2434.3	4.9265	.49915E-03	.67514E-03	.12088E-02	.41294E+00	1.5159	.8467
1860	.49880E+01	.56707	2458.0	2449.2	4.9345	.50616E-03	.68648E-03	.12377E-02	.40895E+00	1.5245	.8455
1870	.51610E+01	.56431	2473.3	2464.2	4.9426	.51339E-03	.69818E-03	.12678E-02	.40495E+00	1.5334	.8444
1880	.53381E+01	.5615J	2488.7	2479.2	4.9506	.52085E-03	.71025E-03	.12991E-02	.40094E+00	1.5425	.8433
1890	.55193E+01	.55872	2504.2	2494.3	4.9587	.52854E-03	.72272E-03	.13316E-02	.39691E+00	1.5519	.8423
1900	.57047E+01	.55589	2519.7	2509.5	4.9667	.53647E-03	.73560E-03	.13655E-02	.39287E+00	1.5616	.8413
1910	.58942E+01	.55304	2535.4	2524.7	4.9747	.54466E-03	.74892E-03	.14008E-02	.38882E+00	1.5717	.8403
1920	.60879E+01	.55017	2551.1	2540.1	4.9828	.55312E-03	.76269E-03	.14376E-02	.38476E+00	1.5820	.8393
1930	.62859E+01	.54727	2567.0	2555.5	4.9908	.56187E-03	.77694E-03	.14760E-02	.38068E+00	1.5927	.8384
1940	.64882E+01	.54434	2582.9	2571.0	4.9989	.57091E-03	.79170E-03	.15160E-02	.37659E+00	1.6038	.8375
1950	.66948E+01	.54139	2599.0	2586.6	5.0069	.58027E-03	.80699E-03	.15578E-02	.37248E+00	1.6152	.8367
1960	.69056E+01	.53841	2615.1	2602.3	5.0150	.58996E-03	.82285E-03	.16016E-02	.36837E+00	1.6271	.8360
1970	.71211E+01	.53540	2631.4	2618.1	5.0231	.60000E-03	.83930E-03	.16473E-02	.36423E+00	1.6394	.8353
1980	.73409E+01	.53237	2647.8	2634.0	5.0311	.61040E-03	.85638E-03	.16952E-02	.36008E+00	1.6521	.8346
1990	.75652E+01	.52930	2664.3	2650.0	5.0392	.62120E-03	.87412E-03	.17453E-02	.35592E+00	1.6653	.8340
2000	.77939E+01	.52621	2680.9	2666.1	5.0474	.63240E-03	.89257E-03	.17979E-02	.35174E+00	1.6790	.8335
2010	.80272E+01	.52308	2697.6	2682.3	5.0555	.64404E-03	.91177E-03	.18531E-02	.34755E+00	1.6932	.8331
2020	.82651E+01	.5199J	2714.5	2698.6	5.0636	.65614E-03	.93176E-03	.19111E-02	.34333E+00	1.7080	.8327
2030	.85075E+01	.51674	2731.5	2715.0	5.0718	.66873E-03	.95260E-03	.19720E-02	.33911E+00	1.7233	.8325
2040	.87546E+01	.51351	2748.6	2731.6	5.0800	.68184E-03	.9743JE-03	.20362E-02	.33486E+00	1.7393	.8323
2050	.90063E+01	.51026	2765.9	2748.2	5.0882	.69550E-03	.99703E-03	.21037E-02	.33060E+00	1.7560	.8322

PROPERTIES OF SATURATED SODIUM LIQUID

TSAT (K)	PSAT (MPA)	HHOL (G/CC)	HLIQ (J/G)	ELIQ (J/G)	SLIQ (J/G-K)	ALPHAP (K-1)	BETAS (MPA-1)	BETAT (MPA-1)	GAMMAV (MPA/K)	CP (J/G-K)	CV (J/G-K)
2060	.92627E+01	.50696	2783.3	2765.0	5.0964	.70974E-03	.10208E-02	.21750E-02	.32632E+00	1.7734	.8323
2070	.95238E+01	.50363	2800.9	2782.0	5.1047	.72462E-03	.10456E-02	.22502E-02	.32202E+00	1.7915	.8324
2080	.97896E+01	.50026	2818.6	2799.1	5.1130	.74017E-03	.10716E-02	.23297E-02	.31771E+00	1.8105	.8327
2090	.10060E+02	.49685	2836.5	2816.3	5.1213	.75643E-03	.10988E-02	.24138E-02	.31337E+00	1.8303	.8332
2100	.10336E+02	.49340	2854.6	2833.6	5.1296	.77346E-03	.11274E-02	.25030E-02	.30902E+00	1.8510	.8337
2110	.10616E+02	.48990	2872.8	2851.2	5.1380	.79131E-03	.11574E-02	.25975E-02	.30464E+00	1.8727	.8345
2120	.10901E+02	.48636	2891.3	2868.9	5.1465	.81005E-03	.11891E-02	.26980E-02	.30024E+00	1.8955	.8354
2130	.11191E+02	.48278	2909.9	2886.7	5.1550	.82975E-03	.12224E-02	.28049E-02	.29583E+00	1.9195	.8365
2140	.11485E+02	.47914	2928.7	2904.8	5.1635	.85047E-03	.12575E-02	.29187E-02	.29139E+00	1.9447	.8379
2150	.11785E+02	.47546	2947.8	2923.0	5.1721	.87231E-03	.12947E-02	.30402E-02	.28692E+00	1.9712	.8394
2160	.12090E+02	.47172	2967.1	2941.4	5.1807	.89535E-03	.13340E-02	.31701E-02	.28244E+00	1.9992	.8412
2170	.12399E+02	.46793	2986.6	2960.1	5.1894	.91970E-03	.13750E-02	.33092E-02	.27793E+00	2.0287	.8433
2180	.12714E+02	.46408	3006.3	2978.9	5.1982	.94548E-03	.14199E-02	.34584E-02	.27339E+00	2.0600	.8457
2190	.13033E+02	.46017	3026.3	2998.0	5.2070	.97281E-03	.14669E-02	.36187E-02	.26883E+00	2.0931	.8485
2200	.13358E+02	.45620	3046.6	3017.3	5.2160	.10019E-02	.15171E-02	.37915E-02	.26424E+00	2.1282	.8516
2210	.13687E+02	.45216	3067.2	3036.9	5.2250	.10328E-02	.15707E-02	.39780E-02	.25962E+00	2.1656	.8551
2220	.14022E+02	.44805	3088.0	3056.7	5.2340	.10657E-02	.16280E-02	.41798E-02	.25497E+00	2.2054	.8590
2230	.14361E+02	.44387	3109.2	3076.9	5.2432	.11010E-02	.16896E-02	.43987E-02	.25029E+00	2.2479	.8634
2240	.14706E+02	.43961	3130.7	3097.3	5.2525	.11387E-02	.17559E-02	.46368E-02	.24558E+00	2.2934	.8684
2250	.15056E+02	.43527	3152.6	3118.0	5.2619	.11793E-02	.18273E-02	.48966E-02	.24084E+00	2.3422	.8741
2260	.15411E+02	.43085	3174.9	3139.1	5.2714	.12230E-02	.19047E-02	.51809E-02	.23605E+00	2.3947	.8804
2270	.15771E+02	.42633	3197.6	3160.6	5.2811	.12702E-02	.19887E-02	.54930E-02	.23124E+00	2.4514	.8875
2280	.16136E+02	.42171	3220.8	3182.5	5.2909	.13213E-02	.20802E-02	.58369E-02	.22638E+00	2.5127	.8955
2290	.16506E+02	.41699	3244.4	3204.8	5.3008	.13770E-02	.21803E-02	.62173E-02	.22147E+00	2.5793	.9045
2300	.16881E+02	.41216	3268.5	3227.5	5.3109	.14377E-02	.22902E-02	.66400E-02	.21653E+00	2.6519	.9147
2310	.17262E+02	.40720	3293.2	3250.8	5.3212	.15043E-02	.24116E-02	.71118E-02	.21153E+00	2.7313	.9262
2320	.17648E+02	.40212	3318.5	3274.6	5.3318	.15777E-02	.25461E-02	.76410E-02	.20648E+00	2.8187	.9393
2330	.18038E+02	.39690	3344.4	3299.0	5.3425	.16590E-02	.26962E-02	.82382E-02	.20137E+00	2.9153	.9541

PROPERTIES OF SATURATED SODIUM LIQUID

TSAT (K)	PSAT (MPA)	RMOL (G/CC)	MLIQ (J/G)	ELIQ (J/G)	SLIQ (J/G-K)	ALPHAP (K-1)	BETAS (MPA-1)	BETAT (MPA-1)	GAMMAV (MPA/K)	CP (J/G-K)	CV (J/G-K)
2340	.18435E+02	.39152	3371.1	3324.1	5.3535	.17494E-02	.28647E-02	.89161E-02	.19621E+00	3.0226	.9711
2350	.18836E+02	.38598	3398.6	3349.6	5.3648	.18507E-02	.30552E-02	.96913E-02	.19097E+00	3.1426	.9907
2360	.19242E+02	.38025	3427.0	3376.4	5.3764	.19651E-02	.32723E-02	.10585E-01	.18566E+00	3.2777	1.0133
2370	.19654E+02	.37432	3456.4	3403.9	5.3883	.20953E-02	.35219E-02	.11623E-01	.18027E+00	3.4312	1.0397
2380	.20071E+02	.36816	3486.9	3432.4	5.4007	.22448E-02	.38121E-02	.12843E-01	.17478E+00	3.6070	1.0706
2390	.20493E+02	.36175	3518.7	3462.0	5.4136	.24183E-02	.41535E-02	.14293E-01	.16919E+00	3.8106	1.1073
2400	.20921E+02	.35505	3552.0	3493.0	5.4270	.26224E-02	.45610E-02	.16041E-01	.16348E+00	4.0495	1.1514
2410	.21353E+02	.34801	3586.9	3525.6	5.4410	.28660E-02	.50559E-02	.18181E-01	.15764E+00	4.3339	1.2052
2420	.21791E+02	.34058	3624.0	3560.0	5.4558	.31623E-02	.56698E-02	.20856E-01	.15162E+00	4.6789	1.2720
2430	.22234E+02	.33270	3663.5	3596.6	5.4715	.35307E-02	.64512E-02	.24280E-01	.14542E+00	5.1069	1.3569
2440	.22683E+02	.32426	3706.0	3636.1	5.4885	.40024E-02	.74797E-02	.28803E-01	.13896E+00	5.6534	1.4681
2450	.23137E+02	.31511	3752.5	3679.1	5.5069	.46296E-02	.88945E-02	.35022E-01	.13219E+00	6.3782	1.6199
2460	.23595E+02	.30506	3804.2	3726.8	5.5273	.55084E-02	.10964E-01	.44066E-01	.12500E+00	7.3915	1.8390
2470	.24060E+02	.29377	3863.3	3781.4	5.5507	.68384E-02	.14277E-01	.58347E-01	.11720E+00	8.9221	2.1832
2480	.24529E+02	.28060	3934.1	3846.7	5.5786	.91237E-02	.20441E-01	.84153E-01	.10842E+00	11.5473	2.8048
2490	.25004E+02	.26413	4026.8	3932.2	5.6153	.14179E-01	.35906E-01	.14521E+00	.97646E-01	17.3398	4.2876
2500	.25484E+02	.23853	4188.3	4081.5	5.6794	.41398E-01	.14650E+00	.52221E+00	.79275E-01	47.8072	13.4113
2503.3	.25641E+02	.21342	4443.0	4322.9					.48432E-01

APPENDIX B

Tabulation of Saturated Sodium Vapor Properties

<u>Property</u>	<u>Symbol</u>	<u>Units</u>
Temperature	TSAT	K
Pressure	PSAT	MPa
Density	RHOV	g/cm ³
Enthalpy	HVAP	J/g
Internal Energy	EVAP	J/g
Vapor Entropy	SVAP	J/g·K
Thermal-Expansion Coefficient	ALPHAP	K ⁻¹
Adiabatic Compressibility	BETAS	MPa ⁻¹
Isothermal Compressibility	BETAT	MPa ⁻¹
Thermal Pressure Coefficient	GAMMAV	MPa/K
Constant-Pressure Specific Heat	CP	J/g·K
Constant-Volume Specific Heat	CV	J/g·K

PROPERTIES OF SATURATED SODIUM VAPOR

TSAT (K)	PSAT (MPA)	RHOV (G/CC)	HVAP (J/G)	EVAP (J/G)	SVAP (J/G-K)	ALPHAP (K-1)	BETAS (MPA-1)	BETAT (MPA-1)	GAMMAV (MPA/K)	CP (J/G-K)	CV (J/G-K)
380	.26303E-10	.19146E-12	5002.8	4865.4	14.7029	.26574E-02	.23881E+11	.38034E+11	.69870E-13	.9899	.6215
390	.61660E-10	.43742E-12	5011.5	4870.5	14.4218	.25950E-02	.10264E+11	.16226E+11	.15993E-12	1.0067	.6368
400	.13847E-09	.95790E-12	5020.1	4875.5	14.1555	.25366E-02	.46073E+10	.72261E+10	.35103E-12	1.0256	.6539
410	.29885E-09	.20172E-11	5028.6	4880.5	13.9028	.24819E-02	.21528E+10	.33487E+10	.74115E-12	1.0464	.6727
420	.62160E-09	.40965E-11	5037.1	4885.3	13.6627	.24307E-02	.10441E+10	.16103E+10	.15095E-11	1.0693	.6933
430	.12492E-08	.80431E-11	5045.4	4890.1	13.4344	.23829E-02	.52414E+09	.80138E+09	.29735E-11	1.0943	.7157
440	.24316E-08	.15303E-10	5053.7	4894.8	13.2169	.23382E-02	.27171E+09	.41180E+09	.56779E-11	1.1213	.7398
450	.45939E-08	.26276E-10	5061.9	4899.4	13.0095	.22964E-02	.14512E+09	.21803E+09	.10533E-10	1.1503	.7656
460	.84400E-08	.50836E-10	5069.9	4903.9	12.8116	.22575E-02	.79699E+08	.11871E+09	.19017E-10	1.1812	.7931
470	.15107E-07	.89084E-10	5077.9	4908.3	12.6224	.22211E-02	.44921E+08	.66342E+08	.33480E-10	1.2140	.8220
480	.26385E-07	.15241E-09	5085.7	4912.6	12.4415	.21873E-02	.25941E+08	.37997E+08	.57564E-10	1.2486	.8525
490	.45037E-07	.25494E-09	5093.4	4916.7	12.2683	.21557E-02	.15325E+08	.22269E+08	.96803E-10	1.2849	.8842
500	.75234E-07	.41754E-09	5101.0	4920.8	12.1023	.21264E-02	.92479E+07	.13337E+08	.15944E-09	1.3227	.9172
510	.12315E-06	.67039E-09	5108.4	4924.7	11.9430	.20990E-02	.56933E+07	.81516E+07	.25750E-09	1.3619	.9512
520	.19775E-06	.10564E-08	5115.6	4928.4	11.7901	.20737E-02	.35714E+07	.50788E+07	.40830E-09	1.4025	.9862
530	.31188E-06	.16356E-08	5122.8	4932.1	11.6431	.20501E-02	.22803E+07	.32221E+07	.63625E-09	1.4442	1.0220
540	.48355E-06	.24904E-08	5129.7	4935.6	11.5018	.20281E-02	.14804E+07	.20794E+07	.97533E-09	1.4868	1.0585
550	.73773E-06	.37329E-08	5136.6	4938.9	11.3658	.20077E-02	.97630E+06	.13638E+07	.14721E-08	1.5304	1.0955
560	.11085E-05	.55126E-08	5143.2	4942.2	11.2348	.19888E-02	.65349E+06	.90829E+06	.21896E-08	1.5746	1.1329
570	.16417E-05	.80275E-08	5149.7	4945.2	11.1085	.19712E-02	.44361E+06	.61373E+06	.32118E-08	1.6193	1.1704
580	.23983E-05	.11534E-07	5156.1	4948.2	10.9867	.19548E-02	.30517E+06	.42043E+06	.46494E-08	1.6643	1.2081
590	.34584E-05	.16365E-07	5162.3	4950.9	10.8691	.19395E-02	.21260E+06	.29179E+06	.66468E-08	1.7096	1.2456
600	.49259E-05	.22942E-07	5168.3	4953.6	10.7556	.19252E-02	.14989E+06	.20504E+06	.93896E-08	1.7549	1.2829
610	.69343E-05	.31777E-07	5174.2	4956.1	10.6458	.19119E-02	.10689E+06	.14578E+06	.13115E-07	1.8001	1.3199
620	.96532E-05	.43594E-07	5179.9	4958.4	10.5397	.18994E-02	.77059E+05	.10482E+06	.18121E-07	1.8451	1.3564
630	.13296E-04	.59154E-07	5185.4	4960.7	10.4371	.18877E-02	.56127E+05	.76175E+05	.24781E-07	1.8896	1.3923
640	.18129E-04	.79483E-07	5190.8	4962.8	10.3377	.18766E-02	.41285E+05	.55924E+05	.33556E-07	1.9336	1.4275
650	.24481E-04	.10580E-06	5196.1	4964.7	10.2415	.18662E-02	.30654E+05	.41457E+05	.45014E-07	1.9769	1.4618

PROPERTIES OF SATURATED SODIUM VAPOR

TSAT (K)	PSAT (MPA)	RHOV (G/CC)	HVAP (J/G)	EVAP (J/G)	SVAP (J/G-K)	ALPHAP (K-1)	BETAS (MPA-1)	BETAT (MPA-1)	GAMMAV (MPA/K)	CP (J/G-K)	CV (J/G-K)
660	.32755E-04	.13959E-06	5201.2	4966.6	10.1482	.18562E-02	.22965E+05	.31018E+05	.59844E-07	2.0195	1.4452
670	.43442E-04	.18259E-06	5206.2	4968.3	10.0579	.18468E-02	.17353E+05	.23414E+05	.78877E-07	2.0611	1.5276
680	.57132E-04	.23691E-06	5211.0	4969.8	9.9702	.18377E-02	.13220E+05	.17823E+05	.10311E-06	2.1017	1.5589
690	.74535E-04	.30500E-06	5215.7	4971.3	9.8852	.18291E-02	.10150E+05	.13678E+05	.13372E-06	2.1413	1.5890
700	.96492E-04	.38974E-06	5220.3	4972.7	9.8027	.18207E-02	.78518E+04	.10578E+05	.17212E-06	2.1796	1.6179
710	.12400E-03	.49450E-06	5224.7	4973.9	9.7225	.18125E-02	.61177E+04	.82415E+04	.21992E-06	2.2167	1.6455
720	.15823E-03	.62314E-06	5229.0	4975.1	9.6447	.18045E-02	.47995E+04	.64668E+04	.27905E-06	2.2525	1.6717
730	.20054E-03	.78013E-06	5233.2	4976.1	9.5691	.17967E-02	.37903E+04	.51088E+04	.35170E-06	2.2869	1.6967
740	.25253E-03	.97056E-06	5237.3	4977.1	9.4957	.17891E-02	.30123E+04	.40624E+04	.44040E-06	2.3197	1.7201
750	.31601E-03	.12002E-05	5241.3	4978.0	9.4242	.17815E-02	.24084E+04	.32505E+04	.54806E-06	2.3505	1.7416
760	.39309E-03	.14757E-05	5245.1	4978.7	9.3548	.17739E-02	.19369E+04	.26166E+04	.67796E-06	2.3799	1.7617
770	.48616E-03	.18043E-05	5248.9	4979.5	9.2872	.17664E-02	.15665E+04	.21185E+04	.83382E-06	2.4079	1.7805
780	.59796E-03	.21944E-05	5252.6	4980.1	9.2214	.17589E-02	.12738E+04	.17247E+04	.10198E-05	2.4344	1.7979
790	.73156E-03	.26552E-05	5256.2	4980.7	9.1575	.17514E-02	.10413E+04	.14117E+04	.12407E-05	2.4594	1.8141
800	.89044E-03	.31969E-05	5259.7	4981.2	9.0952	.17439E-02	.85545E+03	.11614E+04	.15015E-05	2.4830	1.8289
810	.10785E-02	.38310E-05	5263.1	4981.6	9.0345	.17363E-02	.70621E+03	.96020E+03	.18082E-05	2.5051	1.8424
820	.13001E-02	.45698E-05	5266.5	4982.0	8.9754	.17286E-02	.58573E+03	.79764E+03	.21671E-05	2.5257	1.8547
830	.15600E-02	.54271E-05	5269.8	4982.4	8.9179	.17208E-02	.48799E+03	.66565E+03	.25852E-05	2.5448	1.8656
840	.18637E-02	.64180E-05	5273.1	4982.7	8.8619	.17130E-02	.40833E+03	.55795E+03	.30702E-05	2.5625	1.8753
850	.22171E-02	.75588E-05	5276.3	4983.0	8.8073	.17051E-02	.34311E+03	.46968E+03	.36304E-05	2.5788	1.8838
860	.26266E-02	.88673E-05	5279.4	4983.2	8.7540	.16971E-02	.28947E+03	.39699E+03	.42749E-05	2.5936	1.8911
870	.30995E-02	.10363E-04	5282.6	4983.5	8.7022	.16890E-02	.24517E+03	.33689E+03	.50135E-05	2.6071	1.8973
880	.36435E-02	.12066E-04	5285.6	4983.7	8.6516	.16808E-02	.20844E+03	.28698E+03	.58568E-05	2.6192	1.9024
890	.42673E-02	.13999E-04	5288.7	4983.9	8.6023	.16725E-02	.17786E+03	.24537E+03	.68162E-05	2.6300	1.9064
900	.49799E-02	.16186E-04	5291.7	4984.1	8.5542	.16641E-02	.15230E+03	.21055E+03	.79038E-05	2.6396	1.9093
910	.57916E-02	.18653E-04	5294.7	4984.3	8.5073	.16556E-02	.13086E+03	.18129E+03	.91327E-05	2.6479	1.9113
920	.67130E-02	.21427E-04	5297.7	4984.4	8.4615	.16471E-02	.11281E+03	.15661E+03	.10517E-04	2.6550	1.9124
930	.77560E-02	.24537E-04	5300.7	4984.6	8.4169	.16384E-02	.97559E+02	.13574E+03	.12070E-04	2.6610	1.9125

PROPERTIES OF SATURATED SODIUM VAPOR

TSAT (K)	PSAT (MPA)	RHOV (G/LC)	HVAP (J/G)	EVAP (J/G)	SVAP (J/G-K)	ALPHAP (K-1)	BETAS (MPA-1)	BETAT (MPA-1)	GAMMAV (MPA/K)	CP (J/G-K)	CV (J/G-K)
940	.89330E-02	.28014E-04	5303.7	4984.8	8.3733	.16297E-02	.84633E+02	.11801E+03	.13809E-04	2.6659	1.9118
950	.10257E-01	.31891E-04	5306.6	4985.0	8.3308	.16209E-02	.73639E+02	.10291E+03	.15750E-04	2.6697	1.9103
960	.11744E-01	.36202E-04	5309.6	4985.2	8.2893	.16121E-02	.64260E+02	.90008E+02	.17910E-04	2.6726	1.9081
970	.13407E-01	.40985E-04	5312.6	4985.4	8.2488	.16032E-02	.56233E+02	.78946E+02	.20307E-04	2.6745	1.9051
980	.15264E-01	.46276E-04	5315.5	4985.7	8.2093	.15942E-02	.49343E+02	.69433E+02	.22961E-04	2.6755	1.9014
990	.17332E-01	.52117E-04	5318.5	4985.9	8.1707	.15853E-02	.43413E+02	.61230E+02	.25890E-04	2.6757	1.8971
1000	.19629E-01	.58549E-04	5321.4	4986.2	8.1330	.15763E-02	.38293E+02	.54136E+02	.29117E-04	2.6751	1.8922
1010	.22175E-01	.65617E-04	5324.4	4986.5	8.0961	.15673E-02	.33861E+02	.47985E+02	.32663E-04	2.6737	1.8867
1020	.24989E-01	.73366E-04	5327.4	4986.8	8.0602	.15583E-02	.30015E+02	.42636E+02	.36550E-04	2.6716	1.8808
1030	.28095E-01	.81845E-04	5330.3	4987.1	8.0250	.15494E-02	.26608E+02	.37973E+02	.40801E-04	2.6689	1.8743
1040	.31514E-01	.91103E-04	5333.3	4987.4	7.9906	.15404E-02	.23748E+02	.33898E+02	.45442E-04	2.6655	1.8674
1050	.35270E-01	.10119E-03	5336.3	4987.8	7.9571	.15315E-02	.21195E+02	.30328E+02	.50498E-04	2.6617	1.8601
1060	.39388E-01	.11216E-03	5339.3	4988.2	7.9242	.15226E-02	.18957E+02	.27193E+02	.55993E-04	2.6572	1.8525
1070	.43894E-01	.12408E-03	5342.3	4988.6	7.8921	.15138E-02	.16991E+02	.24434E+02	.61956E-04	2.6524	1.8445
1080	.48816E-01	.13699E-03	5345.4	4989.0	7.8607	.15051E-02	.15260E+02	.21999E+02	.68414E-04	2.6471	1.8362
1090	.54181E-01	.15095E-03	5348.4	4989.4	7.8300	.14964E-02	.13733E+02	.19847E+02	.75395E-04	2.6414	1.8276
1100	.60020E-01	.16603E-03	5351.4	4989.9	7.8000	.14878E-02	.12382E+02	.17941E+02	.82930E-04	2.6353	1.8188
1110	.66363E-01	.18224E-03	5354.4	4990.4	7.7706	.14794E-02	.11185E+02	.16248E+02	.91047E-04	2.6290	1.8097
1120	.73241E-01	.19979E-03	5357.5	4990.9	7.7419	.14710E-02	.10122E+02	.14743E+02	.99779E-04	2.6224	1.8005
1130	.80689E-01	.21860E-03	5360.5	4991.4	7.7138	.14628E-02	.91763E+01	.13401E+02	.10916E-03	2.6155	1.7910
1140	.88739E-01	.23879E-03	5363.6	4992.0	7.6862	.14547E-02	.83334E+01	.12202E+02	.11921E-03	2.6085	1.7815
1150	.97176E-01	.25970E-03	5367.3	4993.1	7.6598	.14458E-02	.75995E+01	.11157E+02	.12958E-03	2.5990	1.7702
1160	.10637E+00	.28236E-03	5370.6	4993.9	7.6337	.14375E-02	.69335E+01	.10207E+02	.14083E-03	2.5905	1.7597
1170	.11625E+00	.30654E-03	5374.0	4994.8	7.6081	.14293E-02	.63359E+01	.93528E+01	.15262E-03	2.5819	1.7490
1180	.12685E+00	.33231E-03	5377.4	4995.7	7.5831	.14213E-02	.57987E+01	.85836E+01	.16559E-03	2.5732	1.7384
1190	.13820E+00	.35972E-03	5380.8	4996.6	7.5585	.14135E-02	.53150E+01	.78898E+01	.17916E-03	2.5646	1.7276
1200	.15036E+00	.38886E-03	5384.2	4997.5	7.5345	.14059E-02	.48788E+01	.72630E+01	.19357E-03	2.5559	1.7169
1210	.16334E+00	.41978E-03	5387.6	4998.5	7.5109	.13985E-02	.44848E+01	.66958E+01	.20886E-03	2.5473	1.7061

PROPERTIES OF SATURATED SODIUM VAPOR

TSAT (K)	PSAT (MPA)	RHOV (G/CC)	HVAP (J/G)	EVAP (J/G)	SVAP (J/G-K)	ALPHAP (K-1)	BETAS (MPA-1)	BETAT (MPA-1)	GAMMAV (MPA/K)	CP (J/G-K)	CV (J/G-K)
1220	.17720E+00	.45257E-03	5390.9	4999.4	7.4878	.13912E-02	.41284E+01	.61818E+01	.22506E-03	2.5386	1.6954
1230	.19198E+00	.48729E-03	5394.3	5000.3	7.4651	.13842E-02	.38055E+01	.57152E+01	.24220E-03	2.5301	1.6846
1240	.20770E+00	.52403E-03	5397.6	5001.2	7.4429	.13774E-02	.35124E+01	.52911E+01	.26031E-03	2.5215	1.6739
1250	.22443E+00	.56284E-03	5400.9	5002.2	7.4211	.13707E-02	.32462E+01	.49051E+01	.27945E-03	2.5131	1.6632
1260	.23853E+00	.59375E-03	5408.6	5006.8	7.4032	.13586E-02	.30482E+01	.46183E+01	.29418E-03	2.4925	1.6451
1270	.25692E+00	.63575E-03	5412.1	5008.0	7.3823	.13521E-02	.28259E+01	.42950E+01	.31481E-03	2.4838	1.6342
1280	.27641E+00	.67999E-03	5415.6	5009.1	7.3619	.13458E-02	.26229E+01	.39991E+01	.33653E-03	2.4752	1.6234
1290	.29704E+00	.72655E-03	5419.0	5010.2	7.3418	.13397E-02	.24373E+01	.37281E+01	.35936E-03	2.4667	1.6126
1300	.31885E+00	.77549E-03	5422.4	5011.2	7.3221	.13339E-02	.22672E+01	.34795E+01	.38336E-03	2.4584	1.6019
1310	.34190E+00	.82690E-03	5425.7	5012.3	7.3027	.13283E-02	.21114E+01	.32511E+01	.40856E-03	2.4502	1.5912
1320	.36622E+00	.88087E-03	5429.1	5013.3	7.2836	.13228E-02	.19683E+01	.30411E+01	.43499E-03	2.4422	1.5806
1330	.39187E+00	.93746E-03	5432.3	5014.3	7.2649	.13176E-02	.18368E+01	.28478E+01	.46269E-03	2.4343	1.5701
1340	.41889E+00	.99676E-03	5435.5	5015.3	7.2465	.13127E-02	.17158E+01	.26696E+01	.49171E-03	2.4265	1.5596
1350	.44733E+00	.10589E-02	5438.6	5016.2	7.2283	.13079E-02	.16043E+01	.25052E+01	.52208E-03	2.4189	1.5491
1360	.47723E+00	.11238E-02	5441.7	5017.1	7.2105	.13033E-02	.15016E+01	.23533E+01	.55383E-03	2.4114	1.5387
1370	.50866E+00	.11918E-02	5444.8	5018.0	7.1929	.12990E-02	.14067E+01	.22129E+01	.58701E-03	2.4041	1.5283
1380	.54165E+00	.12628E-02	5447.7	5018.8	7.1757	.12948E-02	.13191E+01	.20829E+01	.62166E-03	2.3968	1.5179
1390	.57626E+00	.13369E-02	5450.6	5019.6	7.1587	.12909E-02	.12380E+01	.19624E+01	.65781E-03	2.3897	1.5075
1400	.61254E+00	.14142E-02	5453.4	5020.3	7.1419	.12871E-02	.11629E+01	.18507E+01	.69550E-03	2.3827	1.4972
1410	.65053E+00	.14949E-02	5456.2	5021.0	7.1254	.12836E-02	.10933E+01	.17469E+01	.73477E-03	2.3758	1.4869
1420	.69030E+00	.15790E-02	5458.8	5021.7	7.1092	.12802E-02	.10288E+01	.16505E+01	.77565E-03	2.3689	1.4766
1430	.73188E+00	.16665E-02	5461.4	5022.3	7.0932	.12770E-02	.96885E+00	.15608E+01	.81819E-03	2.3622	1.4663
1440	.77535E+00	.17576E-02	5464.0	5022.8	7.0774	.12740E-02	.91314E+00	.14772E+01	.86241E-03	2.3555	1.4560
1450	.82073E+00	.18524E-02	5466.4	5023.3	7.0618	.12711E-02	.86132E+00	.13993E+01	.90836E-03	2.3488	1.4457
1460	.86810E+00	.19510E-02	5468.8	5023.8	7.0465	.12684E-02	.81306E+00	.13267E+01	.95606E-03	2.3422	1.4354
1470	.91750E+00	.20534E-02	5471.0	5024.2	7.0313	.12658E-02	.76809E+00	.12588E+01	.10056E-02	2.3356	1.4251
1480	.96898E+00	.21598E-02	5473.2	5024.6	7.0164	.12634E-02	.72614E+00	.11954E+01	.10569E-02	2.3290	1.4147
1490	.10226E+01	.22702E-02	5475.3	5024.9	7.0017	.12612E-02	.68698E+00	.11361E+01	.11101E-02	2.3225	1.4043

PROPERTIES OF SATURATED SODIUM VAPOR

TSAT (K)	PSAT (MPA)	RMUV (G/CC)	HVAP (J/G)	EVAP (J/G)	SVAP (J/G-K)	ALPHAP (K-1)	BETAS (MPA-1)	BETAT (MPA-1)	GAMMAV (MPA/K)	CP (J/G-K)	CV (J/G-K)
1500	.10784E+01	.23848E-02	5477.3	5025.1	6.9872	.12590E-02	.65040E+00	.10806E+01	.11651E-02	2.3158	1.3439
1510	.11365E+01	.25030E-02	5479.2	5025.3	6.9728	.12570E-02	.61619E+00	.10285E+01	.12221E-02	2.3092	1.3834
1520	.11968E+01	.26268E-02	5481.1	5025.5	6.9587	.12550E-02	.58418E+00	.97974E+00	.12810E-02	2.3025	1.3729
1530	.12595E+01	.27544E-02	5482.8	5025.5	6.9447	.12532E-02	.55420E+00	.93393E+00	.13419E-02	2.2958	1.3623
1540	.13246E+01	.28865E-02	5484.5	5025.6	6.9309	.12515E-02	.52610E+00	.89089E+00	.14048E-02	2.2889	1.3517
1550	.13922E+01	.30233E-02	5486.0	5025.5	6.9173	.12498E-02	.49975E+00	.85043E+00	.14697E-02	2.2820	1.3410
1560	.14622E+01	.31649E-02	5487.5	5025.4	6.9038	.12483E-02	.47501E+00	.81237E+00	.15366E-02	2.2750	1.3302
1570	.15349E+01	.33113E-02	5488.8	5025.3	6.8905	.12468E-02	.45177E+00	.77652E+00	.16056E-02	2.2678	1.3194
1580	.16101E+01	.34626E-02	5490.1	5025.1	6.8774	.12453E-02	.42993E+00	.74274E+00	.16766E-02	2.2605	1.3085
1590	.16881E+01	.36190E-02	5491.3	5024.8	6.8644	.12439E-02	.40939E+00	.71088E+00	.17498E-02	2.2531	1.2975
1600	.17687E+01	.37806E-02	5492.3	5024.5	6.8516	.12425E-02	.39005E+00	.68082E+00	.18250E-02	2.2454	1.2864
1610	.18521E+01	.39474E-02	5493.3	5024.1	6.8389	.12412E-02	.37183E+00	.65242E+00	.19024E-02	2.2376	1.2753
1620	.19384E+01	.41196E-02	5494.2	5023.7	6.8264	.12398E-02	.35466E+00	.62558E+00	.19819E-02	2.2297	1.2641
1630	.20275E+01	.42973E-02	5495.0	5023.2	6.8140	.12385E-02	.33846E+00	.60019E+00	.20635E-02	2.2214	1.2527
1640	.21196E+01	.44806E-02	5495.7	5022.7	6.8017	.12372E-02	.32318E+00	.57616E+00	.21473E-02	2.2130	1.2413
1650	.22146E+01	.46728E-02	5496.4	5022.0	6.7896	.12369E-02	.31089E+00	.55559E+00	.22263E-02	2.2052	1.2305
1660	.23127E+01	.48764E-02	5496.9	5021.5	6.7777	.12372E-02	.29758E+00	.53399E+00	.23543E-02	2.2026	1.2253
1670	.24139E+01	.51298E-02	5497.4	5020.9	6.7659	.12576E-02	.28499E+00	.51354E+00	.24488E-02	2.2027	1.2201
1680	.25182E+01	.53393E-02	5497.9	5020.3	6.7543	.12581E-02	.27308E+00	.49416E+00	.25460E-02	2.2028	1.2149
1690	.26257E+01	.55549E-02	5498.3	5025.6	6.7428	.12588E-02	.26179E+00	.47577E+00	.26458E-02	2.2030	1.2097
1700	.27364E+01	.57768E-02	5498.7	5025.0	6.7315	.12596E-02	.25111E+00	.45833E+00	.27483E-02	2.2032	1.2045
1710	.28504E+01	.60051E-02	5499.0	5024.3	6.7203	.12606E-02	.24097E+00	.44178E+00	.28535E-02	2.2035	1.2029
1720	.29678E+01	.62399E-02	5499.2	5023.6	6.7093	.12617E-02	.23137E+00	.42606E+00	.29614E-02	2.2038	1.2023
1730	.30886E+01	.64814E-02	5499.4	5022.9	6.6984	.12630E-02	.22225E+00	.41112E+00	.30721E-02	2.2042	1.2186
1740	.32128E+01	.67296E-02	5499.5	5022.1	6.6876	.12644E-02	.21359E+00	.39692E+00	.31855E-02	2.2047	1.2133
1750	.33404E+01	.69846E-02	5499.6	5021.3	6.6770	.12660E-02	.20536E+00	.38341E+00	.33018E-02	2.2053	1.2079
1760	.34716E+01	.72467E-02	5499.6	5020.5	6.6665	.12677E-02	.19754E+00	.37056E+00	.34210E-02	2.2059	1.2026
1770	.36064E+01	.75159E-02	5499.5	5019.7	6.6561	.12696E-02	.19011E+00	.35833E+00	.35431E-02	2.2066	1.1972

PROPERTIES OF SATURATED SODIUM VAPOR

TSAT (K)	PSAT (MPA)	HMUV (G/CC)	HVAP (J/G)	EVAP (J/G)	SVAP (J/G-K)	ALPHAP (K-1)	BETAS (MPA-1)	BETAT (MPA-1)	GAMMAV (MPA/K)	CP (J/G-K)	CV (J/G-K)
1780	.37448E+01	.77923E-02	5499.4	5018.8	6.6458	.12717E-02	.18304E+00	.34668E+00	.36681E-02	2.2573	1.1918
1790	.38869E+01	.80762E-02	5499.2	5017.9	6.6357	.12739E-02	.17630E+00	.33559E+00	.37961E-02	2.2582	1.1863
1800	.40327E+01	.83675E-02	5498.9	5016.9	6.6256	.12763E-02	.16989E+00	.32501E+00	.39271E-02	2.2591	1.1809
1810	.41823E+01	.86666E-02	5498.5	5016.0	6.6157	.12790E-02	.16378E+00	.31493E+00	.40611E-02	2.2602	1.1754
1820	.43356E+01	.89734E-02	5498.1	5015.0	6.6059	.12818E-02	.15796E+00	.30531E+00	.41982E-02	2.2613	1.1699
1830	.44928E+01	.92882E-02	5497.6	5013.9	6.5962	.12848E-02	.15240E+00	.29614E+00	.43384E-02	2.2625	1.1644
1840	.46539E+01	.96111E-02	5497.1	5012.8	6.5866	.12880E-02	.14710E+00	.28739E+00	.44817E-02	2.2639	1.1588
1850	.48190E+01	.99423E-02	5496.4	5011.7	6.5771	.12914E-02	.14204E+00	.27903E+00	.46282E-02	2.2653	1.1532
1860	.49880E+01	.10282E-01	5495.7	5010.6	6.5677	.12951E-02	.13721E+00	.27105E+00	.47779E-02	2.2669	1.1476
1870	.51610E+01	.10630E-01	5494.9	5009.4	6.5584	.12989E-02	.13260E+00	.26343E+00	.49309E-02	2.2687	1.1419
1880	.53381E+01	.10987E-01	5494.0	5008.1	6.5492	.13031E-02	.12819E+00	.25615E+00	.50871E-02	2.2705	1.1363
1890	.55193E+01	.11353E-01	5493.0	5006.8	6.5400	.13074E-02	.12397E+00	.24919E+00	.52467E-02	2.2725	1.1306
1900	.57047E+01	.11728E-01	5491.9	5005.5	6.5310	.13121E-02	.11994E+00	.24254E+00	.54096E-02	2.2747	1.1248
1910	.58942E+01	.12113E-01	5490.8	5004.2	6.5221	.13170E-02	.11608E+00	.23618E+00	.55760E-02	2.2770	1.1191
1920	.60879E+01	.12507E-01	5489.5	5002.7	6.5132	.13222E-02	.11238E+00	.23011E+00	.57458E-02	2.2795	1.1133
1930	.62859E+01	.12910E-01	5488.2	5001.3	6.5044	.13276E-02	.10884E+00	.22430E+00	.59190E-02	2.2822	1.1074
1940	.64882E+01	.13324E-01	5486.7	4999.7	6.4957	.13334E-02	.10545E+00	.21875E+00	.60958E-02	2.2851	1.1016
1950	.66948E+01	.13746E-01	5485.2	4998.2	6.4870	.13396E-02	.10220E+00	.21344E+00	.62762E-02	2.2882	1.0957
1960	.69058E+01	.14182E-01	5483.5	4996.6	6.4784	.13461E-02	.99085E-01	.20836E+00	.64603E-02	2.2915	1.0897
1970	.71211E+01	.14627E-01	5481.7	4994.9	6.4699	.13529E-02	.96097E-01	.20351E+00	.66480E-02	2.2951	1.0838
1980	.73409E+01	.15083E-01	5479.8	4993.1	6.4615	.13601E-02	.93229E-01	.19887E+00	.68394E-02	2.2990	1.0778
1990	.75652E+01	.15550E-01	5477.8	4991.3	6.4531	.13678E-02	.90478E-01	.19443E+00	.70346E-02	2.3031	1.0717
2000	.77939E+01	.16028E-01	5475.7	4989.5	6.4448	.13758E-02	.87835E-01	.19020E+00	.72337E-02	2.3075	1.0656
2010	.80272E+01	.16518E-01	5473.5	4987.5	6.4365	.13844E-02	.85298E-01	.18615E+00	.74367E-02	2.3122	1.0595
2020	.82651E+01	.17021E-01	5471.1	4985.5	6.4283	.13933E-02	.82859E-01	.18229E+00	.76437E-02	2.3173	1.0533
2030	.85075E+01	.17535E-01	5468.6	4983.5	6.4201	.14029E-02	.80516E-01	.17860E+00	.78547E-02	2.3228	1.0471
2040	.87546E+01	.18063E-01	5466.0	4981.3	6.4120	.14129E-02	.78263E-01	.17508E+00	.80699E-02	2.3286	1.0409
2050	.90063E+01	.18604E-01	5463.2	4979.1	6.4039	.14235E-02	.76096E-01	.17173E+00	.82893E-02	2.3349	1.0346

PROPERTIES OF SATURATED SODIUM VAPOR

TSAT (K)	PSAT (MPA)	RHOV (G/CC)	HVAP (J/G)	EVAP (J/G)	SVAP (J/G-K)	ALPHAP (K-1)	BETAS (MPA-1)	BETAT (MPA-1)	GAMMAV (MPA/K)	CP (J/G-K)	CV (J/G-K)
2060	.92627E+01	.19158E-01	5460.3	4976.8	6.3959	.14348E-02	.74011E-01	.16854E+00	.85129E-02	2.3416	1.0283
2070	.95238E+01	.19727E-01	5457.2	4974.4	6.3879	.14467E-02	.72005E-01	.16550E+00	.87410E-02	2.3488	1.0219
2080	.97896E+01	.20309E-01	5454.0	4971.9	6.3799	.14593E-02	.70073E-01	.16262E+00	.89735E-02	2.3565	1.0154
2090	.10060E+02	.20907E-01	5450.5	4969.4	6.3720	.14726E-02	.68213E-01	.15988E+00	.92106E-02	2.3648	1.0090
2100	.10336E+02	.21520E-01	5447.0	4966.7	6.3641	.14868E-02	.66421E-01	.15729E+00	.94524E-02	2.3738	1.0024
2110	.10616E+02	.22149E-01	5443.2	4963.9	6.3562	.15018E-02	.64694E-01	.15484E+00	.96990E-02	2.3834	.9958
2120	.10901E+02	.22795E-01	5439.3	4961.1	6.3484	.15177E-02	.63030E-01	.15253E+00	.99505E-02	2.3937	.9892
2130	.11191E+02	.23458E-01	5435.1	4958.1	6.3405	.15347E-02	.61425E-01	.15036E+00	.10207E-01	2.4048	.9825
2140	.11485E+02	.24139E-01	5430.8	4955.0	6.3327	.15528E-02	.59878E-01	.14832E+00	.10469E-01	2.4168	.9757
2150	.11785E+02	.24839E-01	5426.3	4951.8	6.3249	.15721E-02	.58384E-01	.14642E+00	.10736E-01	2.4298	.9688
2160	.12090E+02	.25558E-01	5421.5	4948.5	6.3170	.15926E-02	.56943E-01	.14466E+00	.11009E-01	2.4437	.9619
2170	.12399E+02	.26298E-01	5416.5	4945.0	6.3092	.16146E-02	.55551E-01	.14303E+00	.11288E-01	2.4588	.9550
2180	.12714E+02	.27059E-01	5411.2	4941.4	6.3014	.16381E-02	.54208E-01	.14155E+00	.11573E-01	2.4752	.9479
2190	.13033E+02	.27842E-01	5405.7	4937.6	6.2935	.16633E-02	.52909E-01	.14020E+00	.11864E-01	2.4929	.9408
2200	.13358E+02	.28649E-01	5399.9	4933.7	6.2857	.16903E-02	.51655E-01	.13899E+00	.12161E-01	2.5121	.9336
2210	.13687E+02	.29481E-01	5393.9	4929.6	6.2778	.17194E-02	.50442E-01	.13794E+00	.12465E-01	2.5330	.9263
2220	.14022E+02	.30339E-01	5387.5	4925.3	6.2698	.17508E-02	.49269E-01	.13703E+00	.12776E-01	2.5557	.9189
2230	.14361E+02	.31224E-01	5380.8	4920.8	6.2619	.17847E-02	.48135E-01	.13628E+00	.13095E-01	2.5805	.9114
2240	.14706E+02	.32139E-01	5373.8	4916.2	6.2539	.18214E-02	.47037E-01	.13570E+00	.13422E-01	2.6077	.9039
2250	.15056E+02	.33086E-01	5366.4	4911.3	6.2458	.18612E-02	.45974E-01	.13529E+00	.13757E-01	2.6374	.8962
2260	.15411E+02	.34066E-01	5358.6	4906.2	6.2376	.19046E-02	.44944E-01	.13508E+00	.14100E-01	2.6701	.8885
2270	.15771E+02	.35082E-01	5350.4	4900.8	6.2294	.19520E-02	.43947E-01	.13506E+00	.14454E-01	2.7062	.8806
2280	.16136E+02	.36137E-01	5341.7	4895.2	6.2211	.20040E-02	.42981E-01	.13526E+00	.14817E-01	2.7461	.8726
2290	.16506E+02	.37233E-01	5332.6	4889.3	6.2127	.20612E-02	.42044E-01	.13569E+00	.15190E-01	2.7903	.8646
2300	.16881E+02	.38374E-01	5323.0	4883.1	6.2042	.21244E-02	.41136E-01	.13639E+00	.15576E-01	2.8396	.8564
2310	.17262E+02	.39565E-01	5312.8	4876.5	6.1955	.21946E-02	.40255E-01	.13739E+00	.15973E-01	2.8948	.8482
2320	.17648E+02	.40810E-01	5302.0	4869.5	6.1867	.22729E-02	.39400E-01	.13872E+00	.16384E-01	2.9568	.8398
2330	.18038E+02	.42115E-01	5290.5	4862.2	6.1777	.23607E-02	.38572E-01	.14043E+00	.16810E-01	3.0270	.8314

PROPERTIES OF SATURATED SODIUM VAPOR

TSAT (K)	PSAT (MPA)	RMUV (G/GC)	HVAP (J/G)	EVAP (J/G)	SVAP (J/G-K)	ALPHAP (K-1)	BETAS (MPA-1)	BETAT (MPA-1)	BAMHAV (MPA/K)	CP (J/G-K)	CV (J/G-K)
2340	.18435E+02	.43485E-01	5278.3	4854.4	6.1685	.24599E-02	.37770E-01	.14258E+00	.17253E-01	3.1067	.8230
2350	.18836E+02	.44930E-01	5265.3	4846.1	6.1591	.25728E-02	.36993E-01	.14525E+00	.17713E-01	3.1981	.8145
2360	.19242E+02	.46457E-01	5251.4	4837.2	6.1494	.27022E-02	.36243E-01	.14853E+00	.18194E-01	3.3036	.8061
2370	.19654E+02	.48078E-01	5236.5	4827.7	6.1395	.28522E-02	.35522E-01	.15255E+00	.18697E-01	3.4266	.7979
2380	.20071E+02	.49808E-01	5220.5	4817.6	6.1291	.30276E-02	.34832E-01	.15748E+00	.19226E-01	3.5714	.7900
2390	.20493E+02	.51663E-01	5203.2	4806.6	6.1184	.32357E-02	.34181E-01	.16354E+00	.19785E-01	3.7440	.7825
2400	.20921E+02	.53666E-01	5184.5	4794.6	6.1072	.34861E-02	.33577E-01	.17107E+00	.20378E-01	3.9529	.7759
2410	.21353E+02	.55846E-01	5164.0	4781.6	6.0954	.37930E-02	.33038E-01	.18051E+00	.21013E-01	4.2101	.7706
2420	.21791E+02	.58242E-01	5141.4	4767.3	6.0828	.41774E-02	.32590E-01	.19253E+00	.21698E-01	4.5336	.7674
2430	.22234E+02	.60908E-01	5116.4	4751.4	6.0695	.46724E-02	.32282E-01	.20819E+00	.22443E-01	4.9515	.7678
2440	.22683E+02	.63921E-01	5088.4	4733.5	6.0550	.53325E-02	.32201E-01	.22919E+00	.23267E-01	5.5102	.7742
2450	.23137E+02	.67400E-01	5056.4	4713.1	6.0391	.62546E-02	.32514E-01	.25853E+00	.24193E-01	6.2918	.7913
2460	.23595E+02	.71538E-01	5019.2	4689.4	6.0212	.76285E-02	.33567E-01	.30197E+00	.25262E-01	7.4555	.8287
2470	.24060E+02	.76678E-01	4974.6	4660.8	6.0006	.98802E-02	.36166E-01	.37224E+00	.26542E-01	9.3566	.9091
2480	.24529E+02	.83542E-01	4918.3	4624.7	5.9755	.14197E-01	.42604E-01	.50388E+00	.28175E-01	12.9711	1.0967
2490	.25004E+02	.94095E-01	4840.0	4574.3	5.9418	.25484E-01	.62108E-01	.83475E+00	.30529E-01	22.2423	1.6549
2500	.25484E+02	.11939E+00	4693.1	4479.6	5.8813	.10949E+00	.19597E+00	.30839E+01	.35502E-01	86.9137	5.5229
2503.3	.25641E+02	.21342E+00	4443.0	4322.9					.48432E-01

“

”

APPENDIX C

Tabulation of Subcooled-liquid Sodium Properties

<u>Property</u>	<u>Symbol</u>	<u>Units</u>
Temperature	T	K
Pressure	P	MPa
Density	RHOL	g/cm ³
Enthalpy	HLIQ	J/g
Internal Energy	ELIQ	J/g
Entropy	SLIQ	J/g·K
Thermal-Expansion Coefficient	ALPHAP	K ⁻¹
Adiabatic Compressibility	BETAS	MPa ⁻¹
Isothermal Compressibility	BETAT	MPa ⁻¹
Thermal Pressure Coefficient	GAMMAV	MPa/K
Constant-Pressure Specific Heat	CP	J/g·K
Constant-Volume Specific Heat	CV	J/g·K

SUBCOOLED SODIUM LIQUID PROPERTIES AT T = 400.0 DEG K

P (MPA)	HHOL (G/CC)	HLIQ (J/G)	ELIQ (J/G)	SLIQ (J/G-K)	ALPHAP (K-1)	BETAS (MPA-1)	BETAT (MPA-1)	GAMMAV (MPA/K)	CP (J/G-K)	CV (J/G-K)
.13847E-09	.92071	527.4	527.4	2.9238	.25328E-03	.17222E-03	.19256E-03	.13153E+01	1.3699	1.2252
10.0	.92247	537.1	526.3	2.9210	.25145E-03	.17028E-03	.19031E-03	.13213E+01	1.3692	1.2252
20.0	.92422	546.9	525.3	2.9183	.24967E-03	.16840E-03	.18811E-03	.13272E+01	1.3686	1.2252
30.0	.92595	556.6	524.2	2.9156	.24793E-03	.16657E-03	.18598E-03	.13331E+01	1.3679	1.2252

SUBCOOLED SODIUM LIQUID PROPERTIES AT T = 500.0 DEG K

P (MPA)	HHOL (G/CC)	HLIQ (J/G)	ELIQ (J/G)	SLIQ (J/G-K)	ALPHAP (K-1)	BETAS (MPA-1)	BETAT (MPA-1)	GAMMAV (MPA/K)	CP (J/G-K)	CV (J/G-K)
.75234E-07	.89727	662.2	662.2	3.2248	.26248E-03	.18353E-03	.21243E-03	.12356E+01	1.3282	1.1475
10.0	.89916	671.9	660.8	3.2219	.26038E-03	.18124E-03	.20964E-03	.12420E+01	1.3273	1.1475
20.0	.90104	681.6	659.4	3.2190	.25834E-03	.17902E-03	.20694E-03	.12484E+01	1.3265	1.1475
30.0	.90289	691.2	658.0	3.2162	.25636E-03	.17686E-03	.20432E-03	.12547E+01	1.3256	1.1475
40.0	.90473	700.9	656.7	3.2133	.25443E-03	.17477E-03	.20178E-03	.12610E+01	1.3248	1.1475
50.0	.90654	710.5	655.4	3.2105	.25255E-03	.17274E-03	.19931E-03	.12671E+01	1.3240	1.1475
60.0	.90834	720.2	654.1	3.2078	.25072E-03	.17076E-03	.19691E-03	.12733E+01	1.3232	1.1475
70.0	.91012	729.8	652.9	3.2050	.24893E-03	.16884E-03	.19459E-03	.12793E+01	1.3225	1.1475
80.0	.91188	739.4	651.7	3.2023	.24720E-03	.16697E-03	.19232E-03	.12853E+01	1.3217	1.1475
90.0	.91363	749.0	650.5	3.1996	.24550E-03	.16516E-03	.19013E-03	.12912E+01	1.3210	1.1475
100.0	.91536	758.6	649.4	3.1969	.24385E-03	.16339E-03	.18799E-03	.12971E+01	1.3203	1.1475
110.0	.91707	768.2	648.2	3.1943	.24224E-03	.16167E-03	.18591E-03	.13030E+01	1.3196	1.1475
120.0	.91877	777.8	647.2	3.1916	.24066E-03	.15999E-03	.18389E-03	.13087E+01	1.3189	1.1475
130.0	.92045	787.3	646.1	3.1890	.23913E-03	.15836E-03	.18192E-03	.13144E+01	1.3182	1.1475
140.0	.92212	796.9	645.1	3.1864	.23763E-03	.15677E-03	.18001E-03	.13201E+01	1.3176	1.1475
150.0	.92377	806.5	644.1	3.1839	.23616E-03	.15522E-03	.17814E-03	.13257E+01	1.3170	1.1475
160.0	.92541	816.0	643.1	3.1813	.23473E-03	.15371E-03	.17633E-03	.13313E+01	1.3163	1.1475
170.0	.92703	825.5	642.1	3.1788	.23334E-03	.15224E-03	.17455E-03	.13368E+01	1.3157	1.1475

SUBCOOLED SODIUM LIQUID PROPERTIES AT T = 600.0 DEG K

P (MPA)	RMOL (G/CC)	MLIQ (J/G)	LLIQ (J/G)	SLIQ (J/G-K)	ALPHAP (K-1)	BETAS (MPA-1)	BETAT (MPA-1)	GAMMAV (MPA/K)	CP (J/G-K)	CV (J/G-K)
.49259E-05	.87362	793.3	793.3	3.4640	.27186E-03	.19603E-03	.23520E-03	.11559E+01	1.2958	1.0800
10.0	.87566	802.9	791.5	3.4609	.26946E-03	.19333E-03	.23176E-03	.11627E+01	1.2947	1.0800
20.0	.87767	812.5	789.7	3.4578	.26714E-03	.19072E-03	.22843E-03	.11694E+01	1.2936	1.0800
30.0	.87967	822.1	788.0	3.4548	.26488E-03	.18819E-03	.22521E-03	.11761E+01	1.2925	1.0800
40.0	.88164	831.6	786.2	3.4518	.26269E-03	.18574E-03	.22210E-03	.11827E+01	1.2914	1.0800
50.0	.88358	841.2	784.6	3.4488	.26055E-03	.18336E-03	.21908E-03	.11893E+01	1.2904	1.0800
60.0	.88551	850.7	783.0	3.4459	.25848E-03	.18105E-03	.21616E-03	.11958E+01	1.2894	1.0800
70.0	.88741	860.3	781.4	3.4430	.25646E-03	.17881E-03	.21332E-03	.12022E+01	1.2885	1.0800
80.0	.88929	869.8	779.8	3.4401	.25450E-03	.17664E-03	.21058E-03	.12086E+01	1.2875	1.0800
90.0	.89116	879.3	778.3	3.4373	.25259E-03	.17452E-03	.20791E-03	.12149E+01	1.2866	1.0800
100.0	.89300	888.8	776.8	3.4344	.25072E-03	.17247E-03	.20532E-03	.12211E+01	1.2857	1.0800
110.0	.89482	898.3	775.4	3.4317	.24891E-03	.17048E-03	.20281E-03	.12273E+01	1.2848	1.0800
120.0	.89663	907.8	774.0	3.4289	.24714E-03	.16854E-03	.20037E-03	.12334E+01	1.2840	1.0800
130.0	.89842	917.3	772.6	3.4261	.24542E-03	.16665E-03	.19800E-03	.12395E+01	1.2832	1.0800
140.0	.90019	926.8	771.3	3.4234	.24374E-03	.16482E-03	.19570E-03	.12455E+01	1.2824	1.0800
150.0	.90194	936.3	770.0	3.4207	.24211E-03	.16303E-03	.19346E-03	.12515E+01	1.2816	1.0800
160.0	.90368	945.8	768.7	3.4181	.24051E-03	.16129E-03	.19128E-03	.12574E+01	1.2808	1.0800
170.0	.90540	955.2	767.5	3.4154	.23895E-03	.15960E-03	.18916E-03	.12632E+01	1.2800	1.0800
180.0	.90710	964.7	766.3	3.4128	.23743E-03	.15795E-03	.18704E-03	.12690E+01	1.2793	1.0800
190.0	.90879	974.1	765.1	3.4102	.23594E-03	.15634E-03	.18508E-03	.12748E+01	1.2786	1.0800
200.0	.91047	983.6	763.9	3.4076	.23449E-03	.15477E-03	.18312E-03	.12805E+01	1.2779	1.0800
250.0	.91863	1030.7	758.5	3.3949	.22771E-03	.14749E-03	.17406E-03	.13082E+01	1.2746	1.0800
300.0	.92647	1077.6	753.8	3.3828	.22164E-03	.14102E-03	.16604E-03	.13348E+01	1.2716	1.0800

SUBCOOLED SODIUM LIQUID PROPERTIES AT T = 700.0 DEG K

P (MPA)	RMOL (G/CC)	MLIQ (J/G)	ELIQ (J/G)	SLIQ (J/G-K)	ALPHAP (K-1)	BETAS (MPA-1)	BETAT (MPA-1)	GAMMAV (MPA/K)	CP (J/G-K)	CV (J/G-K)
.96492E-04	.84978	921.7	921.7	3.6619	.28142E-03	.20991E-03	.26117E-03	.10775E+01	1.2727	1.0229
10.0	.85198	931.1	919.4	3.6586	.27870E-03	.20674E-03	.25694E-03	.10847E+01	1.2712	1.0229
20.0	.85416	940.6	917.2	3.6553	.27606E-03	.20368E-03	.25286E-03	.10917E+01	1.2698	1.0229
30.0	.85630	950.0	915.0	3.6521	.27350E-03	.20072E-03	.24893E-03	.10987E+01	1.2685	1.0229
40.0	.85842	959.5	912.9	3.6489	.27101E-03	.19786E-03	.24512E-03	.11056E+01	1.2672	1.0229
50.0	.86051	968.9	910.8	3.6458	.26861E-03	.19508E-03	.24145E-03	.11125E+01	1.2659	1.0229
60.0	.86258	978.3	908.8	3.6427	.26627E-03	.19240E-03	.23789E-03	.11193E+01	1.2647	1.0229
70.0	.86462	987.8	906.8	3.6396	.26400E-03	.18980E-03	.23445E-03	.11260E+01	1.2635	1.0229
80.0	.86663	997.2	904.9	3.6366	.26179E-03	.18728E-03	.23113E-03	.11327E+01	1.2624	1.0229
90.0	.86862	1006.6	903.0	3.6336	.25964E-03	.18483E-03	.22790E-03	.11393E+01	1.2612	1.0229
100.0	.87059	1016.0	901.2	3.6306	.25756E-03	.18246E-03	.22478E-03	.11458E+01	1.2601	1.0229
110.0	.87254	1025.5	899.4	3.6277	.25553E-03	.18015E-03	.22176E-03	.11523E+01	1.2591	1.0229
120.0	.87446	1034.9	897.6	3.6247	.25355E-03	.17792E-03	.21882E-03	.11587E+01	1.2580	1.0229
130.0	.87636	1044.3	895.9	3.6219	.25163E-03	.17575E-03	.21598E-03	.11651E+01	1.2570	1.0229
140.0	.87825	1053.7	894.3	3.6190	.24976E-03	.17363E-03	.21322E-03	.11714E+01	1.2560	1.0229
150.0	.88011	1063.1	892.6	3.6162	.24793E-03	.17158E-03	.21054E-03	.11776E+01	1.2551	1.0229
160.0	.88195	1072.4	891.0	3.6134	.24615E-03	.16959E-03	.20793E-03	.11838E+01	1.2541	1.0229
170.0	.88378	1081.8	889.5	3.6106	.24442E-03	.16765E-03	.20540E-03	.11900E+01	1.2532	1.0229
180.0	.88558	1091.2	887.9	3.6078	.24273E-03	.16576E-03	.20295E-03	.11960E+01	1.2523	1.0229
190.0	.88737	1100.6	886.5	3.6051	.24108E-03	.16392E-03	.20056E-03	.12021E+01	1.2515	1.0229
200.0	.88914	1109.9	885.0	3.6024	.23948E-03	.16213E-03	.19823E-03	.12081E+01	1.2506	1.0229
250.0	.89775	1156.7	878.2	3.5892	.23199E-03	.15385E-03	.18751E-03	.12372E+01	1.2467	1.0229
300.0	.90599	1203.2	872.1	3.5765	.22533E-03	.14653E-03	.17809E-03	.12653E+01	1.2431	1.0229
350.0	.91390	1249.6	866.7	3.5643	.21935E-03	.14003E-03	.16976E-03	.12922E+01	1.2400	1.0229
400.0	.92152	1295.9	861.8	3.5525	.21398E-03	.13423E-03	.16234E-03	.13181E+01	1.2371	1.0229

SUBCOOLED SODIUM LIQUID PROPERTIES AT T = 800.0 DEG K

P (MPA)	RHOL (G/CC)	HLIQ (J/G)	ELIQ (J/G)	SLIQ (J/G-K)	ALPHAP (K-1)	BETAS (MPA-1)	BETAT (MPA-1)	GAMMAV (MPA/K)	CP (J/G-K)	CV (J/G-K)
.89044E-03	.82580	1048.1	1048.1	3.8307	.29118E-03	.22543E-03	.29083E-03	.10012E+01	1.2560	.9735
10.0	.82818	1057.4	1045.3	3.8272	.28808E-03	.22169E-03	.28561E-03	.10086E+01	1.2542	.9735
20.0	.83053	1066.7	1042.6	3.8237	.28507E-03	.21808E-03	.28058E-03	.10160E+01	1.2525	.9735
30.0	.83284	1076.0	1039.9	3.8203	.28216E-03	.21460E-03	.27573E-03	.10233E+01	1.2509	.9735
40.0	.83512	1085.3	1037.4	3.8169	.27933E-03	.21122E-03	.27105E-03	.10305E+01	1.2493	.9735
50.0	.83737	1094.6	1034.9	3.8136	.27658E-03	.20795E-03	.26653E-03	.10377E+01	1.2477	.9735
60.0	.83959	1103.9	1032.4	3.8103	.27391E-03	.20479E-03	.26215E-03	.10448E+01	1.2462	.9735
70.0	.84177	1113.2	1030.0	3.8071	.27155E-03	.20188E-03	.25817E-03	.10518E+01	1.2450	.9735
80.0	.84393	1122.5	1027.7	3.8039	.26908E-03	.19896E-03	.25415E-03	.10587E+01	1.2436	.9735
90.0	.84606	1131.8	1025.4	3.8007	.26668E-03	.19614E-03	.25028E-03	.10656E+01	1.2422	.9735
100.0	.84817	1141.1	1023.2	3.7976	.26436E-03	.19341E-03	.24653E-03	.10723E+01	1.2409	.9735
110.0	.85024	1150.4	1021.0	3.7945	.26210E-03	.19076E-03	.24290E-03	.10790E+01	1.2396	.9735
120.0	.85230	1159.6	1018.9	3.7914	.25990E-03	.18819E-03	.23939E-03	.10857E+01	1.2384	.9735
130.0	.85433	1168.9	1016.8	3.7884	.25776E-03	.18570E-03	.23599E-03	.10923E+01	1.2372	.9735
140.0	.85633	1178.2	1014.7	3.7854	.25568E-03	.18328E-03	.23270E-03	.10988E+01	1.2360	.9735
150.0	.85831	1187.5	1012.8	3.7824	.25366E-03	.18093E-03	.22950E-03	.11053E+01	1.2348	.9735
160.0	.86027	1196.8	1010.8	3.7795	.25169E-03	.17866E-03	.22641E-03	.11117E+01	1.2337	.9735
170.0	.86221	1206.1	1008.9	3.7765	.24978E-03	.17644E-03	.22340E-03	.11181E+01	1.2326	.9735
180.0	.86412	1215.4	1007.1	3.7737	.24791E-03	.17429E-03	.22049E-03	.11244E+01	1.2316	.9735
190.0	.86602	1224.6	1005.2	3.7708	.24609E-03	.17220E-03	.21766E-03	.11306E+01	1.2305	.9735
200.0	.86789	1233.9	1003.5	3.7680	.24432E-03	.17016E-03	.21491E-03	.11368E+01	1.2295	.9735
250.0	.87699	1280.2	995.1	3.7542	.23610E-03	.16077E-03	.20229E-03	.11671E+01	1.2249	.9735
300.0	.88565	1326.4	987.7	3.7410	.22880E-03	.15253E-03	.19126E-03	.11963E+01	1.2208	.9735
350.0	.89394	1372.5	980.9	3.7284	.22230E-03	.14523E-03	.18157E-03	.12243E+01	1.2171	.9735
400.0	.90190	1418.4	974.9	3.7161	.21646E-03	.13874E-03	.17298E-03	.12513E+01	1.2138	.9735
450.0	.90955	1464.1	969.4	3.7043	.21120E-03	.13294E-03	.16534E-03	.12774E+01	1.2108	.9735
500.0	.91694	1509.7	964.4	3.6929	.20643E-03	.12771E-03	.15849E-03	.13025E+01	1.2081	.9735

SUBCOOLED SODIUM LIQUID PROPERTIES AT T = 900.0 DEG K

P (MPA)	KHOL (G/CC)	HLIQ (J/G)	ELIQ (J/G)	SLIQ (J/G-K)	ALPHAP (K-1)	BETAS (MPA-1)	BETAT (MPA-1)	GAMMAV (MPA/K)	CP (J/G-K)	CV (J/G-K)
.49799E-02	.80170	1173.3	1173.3	3.9782	.30117E-03	.24288E-03	.32425E-03	.92880E+00	1.2513	.9373
10.0	.80428	1182.4	1170.0	3.9745	.29769E-03	.23855E-03	.31793E-03	.93633E+00	1.2492	.9373
20.0	.80681	1191.5	1166.8	3.9708	.29433E-03	.23437E-03	.31186E-03	.94379E+00	1.2471	.9373
30.0	.80931	1200.7	1163.6	3.9672	.29108E-03	.23035E-03	.30602E-03	.95118E+00	1.2452	.9373
40.0	.81177	1209.8	1160.5	3.9636	.28794E-03	.22647E-03	.30041E-03	.95850E+00	1.2432	.9373
50.0	.81419	1218.9	1157.5	3.9601	.28490E-03	.22273E-03	.29500E-03	.96576E+00	1.2414	.9373
60.0	.81657	1228.1	1154.6	3.9566	.28195E-03	.21911E-03	.28979E-03	.97295E+00	1.2396	.9373
70.0	.81892	1237.2	1151.7	3.9532	.27910E-03	.21561E-03	.28477E-03	.98008E+00	1.2379	.9373
80.0	.82124	1246.3	1148.9	3.9498	.27632E-03	.21223E-03	.27992E-03	.98716E+00	1.2362	.9373
90.0	.82352	1255.5	1146.2	3.9464	.27363E-03	.20895E-03	.27524E-03	.99418E+00	1.2346	.9373
100.0	.82577	1264.6	1143.5	3.9431	.27102E-03	.20578E-03	.27071E-03	.10011E+01	1.2330	.9373
110.0	.82799	1273.8	1141.0	3.9399	.26847E-03	.20271E-03	.26633E-03	.10081E+01	1.2314	.9373
120.0	.83018	1283.0	1138.4	3.9367	.26600E-03	.19973E-03	.26209E-03	.10149E+01	1.2299	.9373
130.0	.83234	1292.1	1135.9	3.9335	.26359E-03	.19683E-03	.25799E-03	.10217E+01	1.2285	.9373
140.0	.83447	1301.3	1133.5	3.9303	.26125E-03	.19402E-03	.25401E-03	.10285E+01	1.2270	.9373
150.0	.83658	1310.5	1131.2	3.9272	.25896E-03	.19129E-03	.25016E-03	.10352E+01	1.2257	.9373
160.0	.83866	1319.6	1128.8	3.9241	.25674E-03	.18864E-03	.24642E-03	.10419E+01	1.2243	.9373
170.0	.84072	1328.8	1126.6	3.9211	.25504E-03	.18634E-03	.24325E-03	.10485E+01	1.2235	.9373
180.0	.84275	1338.0	1124.4	3.9181	.25299E-03	.18389E-03	.23981E-03	.10550E+01	1.2223	.9373
190.0	.84476	1347.1	1122.2	3.9151	.25099E-03	.18151E-03	.23648E-03	.10614E+01	1.2211	.9373
200.0	.84674	1356.3	1120.1	3.9121	.24905E-03	.17920E-03	.23325E-03	.10677E+01	1.2199	.9373
250.0	.85635	1402.1	1110.1	3.8978	.24005E-03	.16859E-03	.21845E-03	.10989E+01	1.2145	.9373
300.0	.86547	1447.3	1101.2	3.8841	.23211E-03	.15931E-03	.20562E-03	.11288E+01	1.2097	.9373
350.0	.87417	1493.5	1093.1	3.8709	.22505E-03	.15114E-03	.19439E-03	.11577E+01	1.2055	.9373
400.0	.88248	1539.0	1085.8	3.8583	.21873E-03	.14389E-03	.18449E-03	.11856E+01	1.2017	.9373
450.0	.89046	1584.5	1079.1	3.8461	.21306E-03	.13743E-03	.17572E-03	.12125E+01	1.1984	.9373
500.0	.89814	1629.8	1073.1	3.8344	.20794E-03	.13164E-03	.16789E-03	.12386E+01	1.1953	.9373
600.0	.91272	1720.0	1062.6	3.8119	.19908E-03	.12171E-03	.15455E-03	.12881E+01	1.1901	.9373

SUBCOOLED SODIUM LIQUID PROPERTIES AT T = 1000.0 DEG K

P (MPA)	HHOL (G/CC)	HLIQ (J/G)	ELIQ (J/G)	SLIQ (J/G-K)	ALPHAP (K-1)	BETAS (MPA-1)	BETAT (MPA-1)	GAMMAV (MPA/K)	CP (J/G-K)	CV (J/G-K)
.19629E-01	.77752	1298.7	1298.7	4.1102	.31140E-03	.26265E-03	.36190E-03	.86046E+00	1.2566	.9120
10.0	.78031	1307.5	1294.7	4.1063	.30749E-03	.25758E-03	.35420E-03	.86812E+00	1.2541	.9120
20.0	.78305	1316.4	1290.9	4.1024	.30372E-03	.25270E-03	.34682E-03	.87572E+00	1.2516	.9120
30.0	.78574	1325.3	1287.1	4.0985	.30008E-03	.24802E-03	.33976E-03	.88323E+00	1.2493	.9120
40.0	.78839	1334.2	1283.5	4.0947	.29659E-03	.24352E-03	.33299E-03	.89067E+00	1.2470	.9120
50.0	.79099	1343.2	1280.0	4.0910	.29321E-03	.23919E-03	.32651E-03	.89802E+00	1.2448	.9120
60.0	.79355	1352.1	1276.5	4.0873	.28995E-03	.23503E-03	.32028E-03	.90531E+00	1.2427	.9120
70.0	.79607	1361.1	1273.1	4.0837	.28680E-03	.23101E-03	.31429E-03	.91253E+00	1.2407	.9120
80.0	.79850	1370.0	1269.8	4.0801	.28375E-03	.22714E-03	.30854E-03	.91968E+00	1.2388	.9120
90.0	.80100	1379.0	1266.6	4.0766	.28080E-03	.22340E-03	.30299E-03	.92677E+00	1.2369	.9120
100.0	.80341	1388.0	1263.5	4.0731	.27795E-03	.21979E-03	.29765E-03	.93379E+00	1.2350	.9120
110.0	.80578	1397.0	1260.5	4.0697	.27517E-03	.21630E-03	.29250E-03	.94076E+00	1.2332	.9120
120.0	.80812	1406.0	1257.5	4.0663	.27248E-03	.21293E-03	.28753E-03	.94766E+00	1.2315	.9120
130.0	.81043	1415.0	1254.6	4.0629	.26987E-03	.20966E-03	.28273E-03	.95452E+00	1.2298	.9120
140.0	.81271	1424.0	1251.7	4.0596	.26733E-03	.20649E-03	.27809E-03	.96131E+00	1.2282	.9120
150.0	.81495	1433.0	1248.9	4.0563	.26486E-03	.20342E-03	.27360E-03	.96806E+00	1.2266	.9120
160.0	.81717	1442.0	1246.2	4.0531	.26246E-03	.20045E-03	.26926E-03	.97476E+00	1.2250	.9120
170.0	.81935	1451.1	1243.6	4.0499	.26012E-03	.19756E-03	.26505E-03	.98140E+00	1.2235	.9120
180.0	.82151	1460.1	1241.0	4.0467	.25784E-03	.19475E-03	.26098E-03	.98800E+00	1.2221	.9120
190.0	.82364	1469.1	1238.4	4.0436	.25562E-03	.19203E-03	.25702E-03	.99456E+00	1.2206	.9120
200.0	.82575	1478.2	1236.0	4.0405	.25346E-03	.18938E-03	.25319E-03	.10011E+01	1.2192	.9120
250.0	.83589	1523.4	1224.3	4.0256	.24338E-03	.17718E-03	.23561E-03	.10330E+01	1.2127	.9120
300.0	.84548	1568.6	1213.8	4.0114	.23527E-03	.16699E-03	.22118E-03	.10637E+01	1.2080	.9120
350.0	.85460	1613.9	1204.3	3.9978	.22765E-03	.15784E-03	.20825E-03	.10932E+01	1.2032	.9120
400.0	.86330	1659.0	1195.7	3.9847	.22085E-03	.14977E-03	.19690E-03	.11216E+01	1.1989	.9120
450.0	.87161	1704.1	1187.8	3.9722	.21476E-03	.14260E-03	.18687E-03	.11492E+01	1.1951	.9120
500.0	.87960	1749.1	1180.7	3.9601	.20927E-03	.13619E-03	.17797E-03	.11759E+01	1.1917	.9120
600.0	.89469	1838.8	1168.2	3.9370	.19981E-03	.12524E-03	.16287E-03	.12268E+01	1.1860	.9120

SUBCOOLED SODIUM LIQUID PROPERTIES AT T = 1100.0 DEG K

P (MPA)	HHOL (G/CC)	HLIQ (J/G)	ELIQ (J/G)	SLIQ (J/G-K)	ALPHAP (K-1)	BETAS (MPA-1)	BLTAT (MPA-1)	GAMMAV (MPA/K)	CP (J/G-K)	CV (J/G-K)
.60020E-01	.75330	1424.9	1424.8	4.2305	.32196E-03	.28524E-03	.40459E-03	.79577E+00	1.2683	.8942
10.0	.75630	1433.5	1420.2	4.2263	.31753E-03	.27924E-03	.39514E-03	.80360E+00	1.2653	.8942
20.0	.75926	1442.1	1415.7	4.2221	.31327E-03	.27348E-03	.38610E-03	.81136E+00	1.2624	.8942
30.0	.76216	1450.7	1411.4	4.2180	.30919E-03	.26797E-03	.37750E-03	.81904E+00	1.2597	.8942
40.0	.76501	1459.4	1407.1	4.2140	.30527E-03	.26270E-03	.36930E-03	.82662E+00	1.2570	.8942
50.0	.76782	1468.1	1403.0	4.2100	.30151E-03	.25766E-03	.36148E-03	.83411E+00	1.2545	.8942
60.0	.77057	1476.8	1398.9	4.2061	.29789E-03	.25282E-03	.35400E-03	.84152E+00	1.2520	.8942
70.0	.77327	1485.5	1395.0	4.2023	.29441E-03	.24817E-03	.34684E-03	.84884E+00	1.2497	.8942
80.0	.77593	1494.3	1391.2	4.1985	.29105E-03	.24370E-03	.33998E-03	.85610E+00	1.2474	.8942
90.0	.77855	1503.1	1387.5	4.1948	.28781E-03	.23941E-03	.33340E-03	.86327E+00	1.2452	.8942
100.0	.78112	1511.8	1383.8	4.1911	.28469E-03	.23527E-03	.32708E-03	.87038E+00	1.2431	.8942
110.0	.78366	1520.6	1380.3	4.1875	.28166E-03	.23128E-03	.32101E-03	.87742E+00	1.2411	.8942
120.0	.78615	1529.5	1376.8	4.1840	.27873E-03	.22744E-03	.31517E-03	.88440E+00	1.2391	.8942
130.0	.78861	1538.3	1373.4	4.1804	.27590E-03	.22372E-03	.30954E-03	.89131E+00	1.2372	.8942
140.0	.79104	1547.1	1370.1	4.1770	.27315E-03	.22013E-03	.30412E-03	.89816E+00	1.2353	.8942
150.0	.79343	1556.0	1366.9	4.1735	.27049E-03	.21667E-03	.29890E-03	.90495E+00	1.2335	.8942
160.0	.79578	1564.8	1363.8	4.1701	.26790E-03	.21331E-03	.29385E-03	.91169E+00	1.2318	.8942
170.0	.79810	1573.7	1360.7	4.1668	.26538E-03	.21008E-03	.28897E-03	.91837E+00	1.2301	.8942
180.0	.80039	1582.6	1357.7	4.1635	.26294E-03	.20691E-03	.28426E-03	.92500E+00	1.2284	.8942
190.0	.80265	1591.5	1354.7	4.1602	.26056E-03	.20386E-03	.27970E-03	.93158E+00	1.2268	.8942
200.0	.80488	1600.4	1351.9	4.1570	.25825E-03	.20090E-03	.27529E-03	.93811E+00	1.2253	.8942
250.0	.81562	1644.9	1338.4	4.1414	.24754E-03	.18733E-03	.25518E-03	.97007E+00	1.2180	.8942
300.0	.82572	1689.6	1326.2	4.1266	.23804E-03	.17550E-03	.23780E-03	.10010E+01	1.2116	.8942
350.0	.83528	1734.3	1315.3	4.1125	.22952E-03	.16508E-03	.22261E-03	.10310E+01	1.2058	.8942
400.0	.84435	1779.0	1305.3	4.0991	.22283E-03	.15638E-03	.21020E-03	.10601E+01	1.2019	.8942
450.0	.85303	1823.7	1296.2	4.0861	.21632E-03	.14843E-03	.19881E-03	.10880E+01	1.1977	.8942
500.0	.86133	1868.3	1287.8	4.0737	.21047E-03	.14135E-03	.18873E-03	.11152E+01	1.1939	.8942
600.0	.87696	1957.4	1273.2	4.0501	.20040E-03	.12929E-03	.17171E-03	.11671E+01	1.1875	.8942

SUBCOOLED SODIUM LIQUID PROPERTIES AT T = 1200.0 DEG K

P (MPA)	RHOL (G/CC)	HLIQ (J/G)	ELIQ (J/G)	SLIQ (J/G-K)	ALPHAP (K-1)	BETAS (MPA-1)	BETAT (MPA-1)	GAMMAV (MPA/K)	CP (J/G-K)	CV (J/G-K)
.15036E+00	.72906	1552.6	1552.4	4.3415	.33292E-03	.31130E-03	.45335E-03	.73436E+00	1.2843	.8819
10.0	.73229	1560.7	1547.1	4.3370	.32789E-03	.30414E-03	.44170E-03	.74234E+00	1.2808	.8819
20.0	.73549	1569.0	1541.8	4.3326	.32304E-03	.29724E-03	.43053E-03	.75033E+00	1.2774	.8819
30.0	.73862	1577.4	1536.8	4.3282	.31842E-03	.29068E-03	.41996E-03	.75820E+00	1.2741	.8819
40.0	.74169	1585.8	1531.8	4.3240	.31401E-03	.28444E-03	.40995E-03	.76597E+00	1.2710	.8819
50.0	.74470	1594.2	1527.1	4.3198	.30981E-03	.27849E-03	.40046E-03	.77363E+00	1.2681	.8819
60.0	.74766	1602.6	1522.4	4.3156	.30577E-03	.27282E-03	.39142E-03	.78119E+00	1.2653	.8819
70.0	.75056	1611.1	1517.9	4.3116	.30191E-03	.26739E-03	.38281E-03	.78866E+00	1.2626	.8819
80.0	.75340	1619.6	1513.5	4.3076	.29820E-03	.26219E-03	.37460E-03	.79604E+00	1.2600	.8819
90.0	.75620	1628.2	1509.2	4.3037	.29463E-03	.25721E-03	.36676E-03	.80334E+00	1.2575	.8819
100.0	.75895	1636.7	1505.0	4.2998	.29120E-03	.25244E-03	.35927E-03	.81055E+00	1.2551	.8819
110.0	.76165	1645.3	1500.9	4.2960	.28790E-03	.24785E-03	.35209E-03	.81769E+00	1.2528	.8819
120.0	.76431	1653.9	1496.9	4.2922	.28471E-03	.24344E-03	.34521E-03	.82475E+00	1.2505	.8819
130.0	.76693	1662.5	1493.0	4.2885	.28163E-03	.23919E-03	.33861E-03	.83174E+00	1.2484	.8819
140.0	.76951	1671.2	1489.2	4.2849	.27866E-03	.23511E-03	.33226E-03	.83866E+00	1.2463	.8819
150.0	.77205	1679.8	1485.6	4.2813	.27578E-03	.23116E-03	.32617E-03	.84552E+00	1.2443	.8819
160.0	.77455	1688.5	1481.9	4.2777	.27299E-03	.22736E-03	.32030E-03	.85231E+00	1.2424	.8819
170.0	.77701	1697.2	1478.4	4.2742	.27029E-03	.22369E-03	.31464E-03	.85905E+00	1.2405	.8819
180.0	.77944	1705.9	1475.0	4.2708	.26768E-03	.22014E-03	.30920E-03	.86572E+00	1.2387	.8819
190.0	.78183	1714.6	1471.6	4.2674	.26514E-03	.21670E-03	.30394E-03	.87234E+00	1.2369	.8819
200.0	.78419	1723.3	1468.3	4.2640	.26267E-03	.21338E-03	.29886E-03	.87890E+00	1.2352	.8819
250.0	.79552	1767.1	1452.9	4.2477	.25130E-03	.19824E-03	.27587E-03	.91095E+00	1.2272	.8819
300.0	.80617	1811.1	1439.0	4.2324	.24130E-03	.18516E-03	.25619E-03	.94188E+00	1.2202	.8819
350.0	.81620	1855.2	1426.4	4.2178	.23240E-03	.17372E-03	.23913E-03	.97184E+00	1.2139	.8819
400.0	.82571	1899.5	1415.0	4.2039	.22438E-03	.16361E-03	.22417E-03	.10009E+01	1.2083	.8819
450.0	.83473	1943.7	1404.6	4.1906	.21711E-03	.15461E-03	.21093E-03	.10293E+01	1.2031	.8819
500.0	.84334	1988.0	1395.1	4.1778	.21156E-03	.14711E-03	.20018E-03	.10569E+01	1.2000	.8819
600.0	.85954	2076.4	1378.4	4.1536	.20089E-03	.13367E-03	.18110E-03	.11093E+01	1.1930	.8819

SUBCOOLED SODIUM LIQUID PROPERTIES AT T = 1300.0 DEG K

P (MPA)	HHOL (G/CC)	HLIQ (J/G)	ELIQ (J/G)	SLIQ (J/G-K)	ALPHAP (K-1)	BETAS (MPA-1)	BETAT (MPA-1)	GAMMAV (MPA/K)	CP (J/G-K)	CV (J/G-K)
.31885E+00	.70485	1682.1	1681.6	4.4449	.34436E-03	.34169E-03	.50952E-03	.67586E+00	1.3032	.8740
10.0	.70829	1689.7	1675.6	4.4402	.33865E-03	.33307E-03	.49510E-03	.68400E+00	1.2991	.8740
20.0	.71175	1697.6	1669.5	4.4355	.33307E-03	.32468E-03	.48114E-03	.69226E+00	1.2951	.8740
30.0	.71514	1705.6	1663.7	4.4309	.32780E-03	.31677E-03	.46804E-03	.70038E+00	1.2913	.8740
40.0	.71845	1713.7	1658.0	4.4263	.32283E-03	.30929E-03	.45573E-03	.70838E+00	1.2878	.8740
50.0	.72169	1721.8	1652.5	4.4219	.31809E-03	.30220E-03	.44410E-03	.71625E+00	1.2844	.8740
60.0	.72488	1729.9	1647.2	4.4175	.31357E-03	.29546E-03	.43311E-03	.72400E+00	1.2811	.8740
70.0	.72797	1738.1	1642.0	4.4132	.30927E-03	.28906E-03	.42271E-03	.73164E+00	1.2780	.8740
80.0	.73101	1746.4	1636.9	4.4090	.30516E-03	.28296E-03	.41283E-03	.73918E+00	1.2751	.8740
90.0	.73400	1754.6	1632.0	4.4049	.30122E-03	.27714E-03	.40345E-03	.74662E+00	1.2723	.8740
100.0	.73694	1763.0	1627.3	4.4008	.29746E-03	.27158E-03	.39452E-03	.75397E+00	1.2696	.8740
110.0	.73982	1771.3	1622.6	4.3968	.29384E-03	.26626E-03	.38601E-03	.76123E+00	1.2670	.8740
120.0	.74265	1779.7	1618.1	4.3929	.29028E-03	.26112E-03	.37778E-03	.76840E+00	1.2644	.8740
130.0	.74543	1788.1	1613.7	4.3890	.28703E-03	.25629E-03	.37012E-03	.77549E+00	1.2621	.8740
140.0	.74817	1796.5	1609.4	4.3852	.28380E-03	.25160E-03	.36269E-03	.78251E+00	1.2598	.8740
150.0	.75086	1804.9	1605.2	4.3814	.28070E-03	.24709E-03	.35556E-03	.78944E+00	1.2576	.8740
160.0	.75351	1813.4	1601.1	4.3777	.27770E-03	.24276E-03	.34873E-03	.79631E+00	1.2555	.8740
170.0	.75611	1821.9	1597.0	4.3740	.27480E-03	.23859E-03	.34217E-03	.80311E+00	1.2534	.8740
180.0	.75868	1830.4	1593.1	4.3704	.27200E-03	.23456E-03	.33587E-03	.80984E+00	1.2514	.8740
190.0	.76121	1838.9	1589.3	4.3669	.26929E-03	.23068E-03	.32980E-03	.81651E+00	1.2495	.8740
200.0	.76370	1847.5	1585.6	4.3633	.26666E-03	.22694E-03	.32396E-03	.82312E+00	1.2476	.8740
250.0	.77565	1890.4	1568.1	4.3464	.25463E-03	.20999E-03	.29769E-03	.85533E+00	1.2390	.8740
300.0	.78683	1933.7	1552.4	4.3305	.24413E-03	.19549E-03	.27545E-03	.88630E+00	1.2315	.8740
350.0	.79735	1977.2	1538.2	4.3154	.23485E-03	.18291E-03	.25633E-03	.91621E+00	1.2248	.8740
400.0	.80729	2020.8	1525.3	4.3010	.22654E-03	.17187E-03	.23967E-03	.94521E+00	1.2188	.8740
450.0	.81672	2064.5	1513.6	4.2873	.21904E-03	.16208E-03	.22502E-03	.97341E+00	1.2133	.8740
500.0	.82569	2108.4	1502.8	4.2741	.21221E-03	.15334E-03	.21202E-03	.10009E+01	1.2084	.8740
600.0	.84243	2196.1	1483.9	4.2494	.20131E-03	.13895E-03	.19101E-03	.10539E+01	1.2014	.8740

SUBCOOLED SODIUM LIQUID PROPERTIES AT T = 1400.0 DEG K

P (MPA)	RMOL (G/CC)	HLIQ (J/G)	ELIQ (J/G)	SLIQ (J/G-K)	ALPHAP (K-1)	BETAS (MPA-1)	BETAT (MPA-1)	GAMMAV (MPA/K)	CP (J/G-K)	CV (J/G-K)
.61254E+00	.68069	1813.7	1812.8	4.5421	.35648E-03	.37759E-03	.57496E-03	.62000E+00	1.3242	.8696
10.0	.68432	1820.6	1806.0	4.5372	.34998E-03	.36716E-03	.55708E-03	.62824E+00	1.3194	.8696
20.0	.68808	1828.1	1799.1	4.5322	.34350E-03	.35678E-03	.53938E-03	.63684E+00	1.3147	.8696
30.0	.69174	1835.7	1792.3	4.5273	.33743E-03	.34706E-03	.52293E-03	.64527E+00	1.3103	.8696
40.0	.69532	1843.4	1785.9	4.5224	.33173E-03	.33795E-03	.50759E-03	.65354E+00	1.3061	.8696
50.0	.69880	1851.1	1779.6	4.5177	.32635E-03	.32938E-03	.49323E-03	.66166E+00	1.3022	.8696
60.0	.70221	1858.9	1773.5	4.5131	.32127E-03	.32129E-03	.47976E-03	.66965E+00	1.2985	.8696
70.0	.70554	1866.8	1767.6	4.5086	.31646E-03	.31365E-03	.46710E-03	.67750E+00	1.2951	.8696
80.0	.70880	1874.7	1761.8	4.5041	.31188E-03	.30642E-03	.45515E-03	.68523E+00	1.2917	.8696
90.0	.71200	1882.7	1756.3	4.4998	.30753E-03	.29955E-03	.44387E-03	.69285E+00	1.2886	.8696
100.0	.71512	1890.7	1750.9	4.4955	.30338E-03	.29302E-03	.43319E-03	.70035E+00	1.2856	.8696
110.0	.71819	1898.8	1745.6	4.4913	.29944E-03	.28682E-03	.42308E-03	.70776E+00	1.2828	.8696
120.0	.72120	1906.9	1740.5	4.4871	.29565E-03	.28090E-03	.41345E-03	.71507E+00	1.2800	.8696
130.0	.72416	1915.0	1735.5	4.4831	.29201E-03	.27524E-03	.40429E-03	.72228E+00	1.2774	.8696
140.0	.72706	1923.2	1730.6	4.4791	.28853E-03	.26983E-03	.39556E-03	.72941E+00	1.2749	.8696
150.0	.72991	1931.4	1725.9	4.4751	.28518E-03	.26464E-03	.38723E-03	.73645E+00	1.2724	.8696
160.0	.73271	1939.7	1721.3	4.4713	.28195E-03	.25968E-03	.37927E-03	.74340E+00	1.2701	.8696
170.0	.73547	1947.9	1716.8	4.4674	.27884E-03	.25491E-03	.37165E-03	.75029E+00	1.2679	.8696
180.0	.73818	1956.2	1712.4	4.4637	.27585E-03	.25033E-03	.36435E-03	.75709E+00	1.2657	.8696
190.0	.74085	1964.6	1708.1	4.4600	.27296E-03	.24593E-03	.35735E-03	.76383E+00	1.2636	.8696
200.0	.74347	1972.9	1703.9	4.4563	.27017E-03	.24170E-03	.35064E-03	.77050E+00	1.2616	.8696
250.0	.75604	2015.0	1684.3	4.4387	.25746E-03	.22265E-03	.32066E-03	.80291E+00	1.2524	.8696
300.0	.76770	2057.5	1666.7	4.4222	.24648E-03	.20653E-03	.29555E-03	.83397E+00	1.2445	.8696
350.0	.77877	2100.3	1650.8	4.4066	.23684E-03	.19267E-03	.27416E-03	.86387E+00	1.2374	.8696
400.0	.78914	2143.3	1636.4	4.3917	.22827E-03	.18059E-03	.25568E-03	.89279E+00	1.2312	.8696
450.0	.79896	2186.5	1623.2	4.3776	.22055E-03	.16996E-03	.23951E-03	.92086E+00	1.2255	.8696
500.0	.80830	2229.8	1611.2	4.3641	.21356E-03	.16050E-03	.22523E-03	.94817E+00	1.2203	.8696
600.0	.82567	2316.7	1590.0	4.3388	.20128E-03	.14440E-03	.20111E-03	.10008E+01	1.2112	.8696

SUBCOOLED SODIUM LIQUID PROPERTIES AT T = 1500.0 DEG K

P (MPA)	MMOL (G/CC)	MLIQ (J/G)	ELIQ (J/G)	SLIQ (J/G-K)	ALPHAP (K-1)	BETAS (MPA-1)	BETAT (MPA-1)	GAMMAV (MPA/K)	CP (J/G-K)	CV (J/G-K)
.10784E+01	.65662	1947.5	1945.9	4.6340	.36943E-03	.42064E-03	.65215E-03	.56648E+00	1.3467	.8686
10.0	.66039	1953.7	1938.5	4.6290	.36208E-03	.40799E-03	.63000E-03	.57473E+00	1.3413	.8686
20.0	.66448	1960.6	1930.5	4.6236	.35444E-03	.39486E-03	.60718E-03	.58375E+00	1.3357	.8686
30.0	.66846	1967.7	1922.9	4.6183	.34737E-03	.38272E-03	.58622E-03	.59256E+00	1.3305	.8686
40.0	.67232	1975.0	1915.5	4.6132	.34079E-03	.37143E-03	.56688E-03	.60117E+00	1.3257	.8686
50.0	.67609	1982.3	1908.3	4.6082	.33465E-03	.36091E-03	.54896E-03	.60961E+00	1.3213	.8686
60.0	.67975	1989.7	1901.4	4.6033	.32889E-03	.35106E-03	.53230E-03	.61787E+00	1.3171	.8686
70.0	.68332	1997.2	1894.7	4.5985	.32348E-03	.34183E-03	.51675E-03	.62598E+00	1.3131	.8686
80.0	.68681	2004.8	1888.3	4.5938	.31837E-03	.33315E-03	.50220E-03	.63394E+00	1.3094	.8686
90.0	.69022	2012.4	1882.0	4.5892	.31354E-03	.32496E-03	.48855E-03	.64177E+00	1.3059	.8686
100.0	.69356	2020.1	1875.9	4.5848	.30896E-03	.31723E-03	.47571E-03	.64947E+00	1.3026	.8686
110.0	.69682	2027.9	1870.0	4.5803	.30461E-03	.30990E-03	.46361E-03	.65705E+00	1.2995	.8686
120.0	.70002	2035.7	1864.3	4.5760	.30047E-03	.30295E-03	.45217E-03	.66451E+00	1.2965	.8686
130.0	.70316	2043.6	1858.7	4.5718	.29652E-03	.29635E-03	.44134E-03	.67187E+00	1.2936	.8686
140.0	.70623	2051.5	1853.2	4.5676	.29275E-03	.29006E-03	.43107E-03	.67912E+00	1.2909	.8686
150.0	.70925	2059.4	1848.0	4.5635	.28914E-03	.28407E-03	.42131E-03	.68628E+00	1.2883	.8686
160.0	.71221	2067.4	1842.8	4.5594	.28567E-03	.27834E-03	.41202E-03	.69335E+00	1.2856	.8686
170.0	.71511	2075.5	1837.8	4.5554	.28235E-03	.27287E-03	.40316E-03	.70033E+00	1.2834	.8686
180.0	.71797	2083.6	1832.9	4.5515	.27917E-03	.26764E-03	.39474E-03	.70723E+00	1.2811	.8686
190.0	.72078	2091.7	1828.1	4.5477	.27610E-03	.26262E-03	.38666E-03	.71405E+00	1.2789	.8686
200.0	.72355	2099.8	1823.4	4.5439	.27313E-03	.25780E-03	.37893E-03	.72079E+00	1.2768	.8686
250.0	.73673	2141.0	1801.6	4.5256	.25975E-03	.23633E-03	.34474E-03	.75346E+00	1.2671	.8686
300.0	.74900	2182.6	1782.1	4.5085	.24831E-03	.21837E-03	.31646E-03	.78464E+00	1.2588	.8686
350.0	.76048	2224.7	1764.5	4.4924	.23834E-03	.20307E-03	.29259E-03	.81457E+00	1.2516	.8686
400.0	.77128	2267.1	1748.5	4.4772	.22952E-03	.18984E-03	.27212E-03	.84345E+00	1.2451	.8686
450.0	.78149	2309.7	1733.9	4.4626	.22163E-03	.17826E-03	.25433E-03	.87140E+00	1.2393	.8686
500.0	.79118	2352.5	1720.5	4.4488	.21450E-03	.16803E-03	.23871E-03	.89855E+00	1.2340	.8686
600.0	.80919	2438.4	1696.9	4.4228	.20204E-03	.15071E-03	.21249E-03	.95082E+00	1.2247	.8686

SUBCOOLED SODIUM LIQUID PROPERTIES AT T = 1600.0 DEG K

P (MPA)	RHOL (G/CC)	HLIQ (J/G)	ELIQ (J/G)	SLIQ (J/G-K)	ALPHAP (K-1)	BETAS (MPA-1)	BETAT (MPA-1)	GAMMAV (MPA/K)	CP (J/G-K)	CV (J/G-K)
.17687E+01	.63268	2083.8	2081.0	4.7212	.38346E-03	.47323E-03	.74456E-03	.51501E+00	1.3705	.8711
10.0	.63649	2088.9	2073.2	4.7163	.37522E-03	.45791E-03	.71728E-03	.52311E+00	1.3645	.8711
20.0	.64098	2095.3	2064.1	4.7105	.36607E-03	.44087E-03	.68722E-03	.53267E+00	1.3578	.8711
30.0	.64531	2101.9	2055.4	4.7049	.35771E-03	.42533E-03	.66003E-03	.54196E+00	1.3517	.8711
40.0	.64950	2108.6	2047.0	4.6994	.35004E-03	.41106E-03	.64528E-03	.55100E+00	1.3462	.8711
50.0	.65356	2115.4	2038.9	4.6941	.34295E-03	.39791E-03	.61262E-03	.55981E+00	1.3411	.8711
60.0	.65751	2122.4	2031.1	4.6889	.33638E-03	.38574E-03	.59178E-03	.56842E+00	1.3364	.8711
70.0	.66135	2129.4	2023.6	4.6839	.33026E-03	.37442E-03	.57253E-03	.57684E+00	1.3320	.8711
80.0	.66509	2136.6	2016.3	4.6789	.32453E-03	.36387E-03	.55468E-03	.58508E+00	1.3279	.8711
90.0	.66873	2143.9	2009.3	4.6741	.31915E-03	.35399E-03	.53806E-03	.59315E+00	1.3240	.8711
100.0	.67228	2151.2	2002.5	4.6694	.31409E-03	.34473E-03	.52255E-03	.60108E+00	1.3204	.8711
110.0	.67576	2158.7	1995.9	4.6648	.30931E-03	.33601E-03	.50802E-03	.60886E+00	1.3170	.8711
120.0	.67915	2166.2	1989.5	4.6602	.30479E-03	.32779E-03	.49438E-03	.61652E+00	1.3138	.8711
130.0	.68247	2173.8	1983.3	4.6558	.30050E-03	.32002E-03	.48154E-03	.62404E+00	1.3107	.8711
140.0	.68572	2181.4	1977.2	4.6514	.29642E-03	.31266E-03	.46942E-03	.63145E+00	1.3078	.8711
150.0	.68891	2189.1	1971.4	4.6471	.29253E-03	.30568E-03	.45797E-03	.63875E+00	1.3050	.8711
160.0	.69204	2196.9	1965.7	4.6429	.28881E-03	.29904E-03	.44712E-03	.64595E+00	1.3024	.8711
170.0	.69510	2204.6	1960.1	4.6388	.28526E-03	.29272E-03	.43682E-03	.65304E+00	1.2999	.8711
180.0	.69811	2212.5	1954.7	4.6347	.28186E-03	.28670E-03	.42704E-03	.66004E+00	1.2975	.8711
190.0	.70106	2220.4	1949.4	4.6307	.27860E-03	.28094E-03	.41772E-03	.66695E+00	1.2951	.8711
200.0	.70397	2228.3	1944.2	4.6268	.27546E-03	.27544E-03	.40883E-03	.67378E+00	1.2929	.8711
250.0	.71778	2266.4	1920.1	4.6079	.26145E-03	.25118E-03	.36992E-03	.70677E+00	1.2830	.8711
300.0	.73058	2309.3	1898.6	4.5903	.24956E-03	.23109E-03	.33811E-03	.73811E+00	1.2745	.8711
350.0	.74253	2350.6	1879.3	4.5737	.23912E-03	.21406E-03	.31131E-03	.76809E+00	1.2668	.8711
400.0	.75375	2392.4	1861.7	4.5580	.23027E-03	.19966E-03	.28895E-03	.79694E+00	1.2606	.8711
450.0	.76433	2434.4	1845.6	4.5431	.22223E-03	.18704E-03	.26944E-03	.82480E+00	1.2548	.8711
500.0	.77436	2476.6	1831.0	4.5289	.21500E-03	.17596E-03	.25240E-03	.85182E+00	1.2495	.8711
600.0	.79299	2561.7	1805.0	4.5023	.20241E-03	.15732E-03	.22398E-03	.90370E+00	1.2401	.8711

SUBCOOLED SODIUM LIQUID PROPERTIES AT T = 1700.0 DEG K

P (MPA)	HHOL (G/CC)	HLIQ (J/G)	ELIQ (J/G)	SLIQ (J/G-K)	ALPHAP (K-1)	BETAS (MPA-1)	BETAT (MPA-1)	GAMMAV (MPA/K)	CP (J/G-K)	CV (J/G-K)
.27364E+01	.60864	2223.1	2218.6	4.8047	.41427E-03	.53891E-03	.87853E-03	.47154E+00	1.4114	.8658
10.0	.61245	2226.7	2216.4	4.7998	.40206E-03	.52119E-03	.84200E-03	.47751E+00	1.3987	.8658
20.0	.61749	2232.1	2199.7	4.7934	.38687E-03	.49896E-03	.79693E-03	.48545E+00	1.3828	.8658
30.0	.62230	2237.8	2189.6	4.7873	.36950E-03	.47571E-03	.74923E-03	.49318E+00	1.3636	.8658
40.0	.62686	2243.9	2180.1	4.7815	.35948E-03	.45657E-03	.71504E-03	.50275E+00	1.3554	.8658
50.0	.63127	2250.2	2171.0	4.7758	.35123E-03	.43988E-03	.68595E-03	.51204E+00	1.3501	.8658
60.0	.63553	2256.7	2162.3	4.7703	.34367E-03	.42463E-03	.65957E-03	.52106E+00	1.3448	.8658
70.0	.63965	2263.3	2153.9	4.7650	.33671E-03	.41061E-03	.63549E-03	.52985E+00	1.3399	.8658
80.0	.64366	2270.0	2145.7	4.7598	.33026E-03	.39767E-03	.61339E-03	.53842E+00	1.3354	.8658
90.0	.64755	2276.9	2137.9	4.7547	.32427E-03	.38567E-03	.59303E-03	.54680E+00	1.3313	.8658
100.0	.65134	2283.9	2130.4	4.7498	.31867E-03	.37451E-03	.57418E-03	.55499E+00	1.3274	.8658
110.0	.65504	2291.0	2123.0	4.7450	.31341E-03	.36409E-03	.55667E-03	.56302E+00	1.3238	.8658
120.0	.65864	2298.2	2116.0	4.7402	.30848E-03	.35432E-03	.54034E-03	.57089E+00	1.3203	.8658
130.0	.66216	2305.4	2109.1	4.7356	.30382E-03	.34515E-03	.52508E-03	.57861E+00	1.3171	.8658
140.0	.66559	2312.8	2102.4	4.7310	.29941E-03	.33652E-03	.51077E-03	.58620E+00	1.3141	.8658
150.0	.66896	2320.2	2095.9	4.7266	.29523E-03	.32838E-03	.49731E-03	.59366E+00	1.3112	.8658
160.0	.67225	2327.6	2089.6	4.7222	.29126E-03	.32067E-03	.48463E-03	.60100E+00	1.3085	.8658
170.0	.67547	2335.2	2083.5	4.7179	.28748E-03	.31337E-03	.47266E-03	.60823E+00	1.3059	.8658
180.0	.67863	2342.8	2077.5	4.7137	.28388E-03	.30644E-03	.46132E-03	.61535E+00	1.3034	.8658
190.0	.68174	2350.4	2071.7	4.7096	.28043E-03	.29985E-03	.45058E-03	.62237E+00	1.3010	.8658
200.0	.68478	2358.1	2066.1	4.7055	.27712E-03	.29357E-03	.44037E-03	.62929E+00	1.2987	.8658
250.0	.69922	2397.3	2039.7	4.6860	.26246E-03	.26612E-03	.39608E-03	.66263E+00	1.2886	.8658
300.0	.71255	2437.3	2016.2	4.6679	.25019E-03	.24376E-03	.36041E-03	.69417E+00	1.2801	.8658
350.0	.72495	2477.9	1995.1	4.6508	.23968E-03	.22511E-03	.33095E-03	.72424E+00	1.2729	.8658
400.0	.73658	2518.9	1975.9	4.6347	.23049E-03	.20925E-03	.30607E-03	.75307E+00	1.2664	.8658
450.0	.74753	2560.4	1958.4	4.6195	.22235E-03	.19556E-03	.28475E-03	.78087E+00	1.2607	.8658
500.0	.75789	2602.1	1942.4	4.6050	.21505E-03	.18360E-03	.26623E-03	.80776E+00	1.2554	.8658
600.0	.77710	2686.2	1914.1	4.5778	.20239E-03	.16363E-03	.23553E-03	.85928E+00	1.2462	.8658

SUBCOOLED SODIUM LIQUID PROPERTIES AT T = 1800.0 DEG K

P (MPA)	RHOL (G/CC)	HLIQ (J/G)	LLIQ (J/G)	SLIQ (J/G-K)	ALPHAP (K-1)	BETAS (MPA-1)	BETAT (MPA-1)	GAMMAV (MPA/K)	CP (J/G-K)	CV (J/G-K)
.40327E+01	.58321	2367.8	2360.9	4.8862	.46696E-03	.62327E-03	.10791E-02	.43273E+00	1.4764	.8527
10.0	.58689	2369.6	2352.6	4.8815	.45279E-03	.60289E-03	.10332E-02	.43825E+00	1.4613	.8527
20.0	.59278	2373.1	2339.3	4.8740	.43164E-03	.57211E-03	.96532E-03	.44715E+00	1.4388	.8527
30.0	.59835	2377.1	2327.0	4.8669	.41315E-03	.54488E-03	.90674E-03	.45564E+00	1.4190	.8527
40.0	.60364	2381.6	2315.3	4.8602	.39681E-03	.52057E-03	.85558E-03	.46379E+00	1.4015	.8527
50.0	.60869	2386.5	2304.4	4.8537	.38224E-03	.49869E-03	.81046E-03	.47163E+00	1.3858	.8527
60.0	.61352	2391.8	2294.0	4.8476	.36913E-03	.47888E-03	.77032E-03	.47919E+00	1.3717	.8527
70.0	.61815	2397.5	2284.2	4.8417	.35726E-03	.46084E-03	.73435E-03	.48650E+00	1.3588	.8527
80.0	.62259	2403.4	2274.9	4.8360	.33540E-03	.43499E-03	.67925E-03	.49378E+00	1.3315	.8527
90.0	.62675	2409.9	2266.3	4.8307	.32870E-03	.42030E-03	.65411E-03	.50251E+00	1.3271	.8527
100.0	.63079	2416.4	2257.9	4.8256	.32250E-03	.40676E-03	.63109E-03	.51102E+00	1.3230	.8527
110.0	.63471	2423.1	2249.8	4.8205	.31674E-03	.39423E-03	.60990E-03	.51933E+00	1.3192	.8527
120.0	.63853	2430.0	2242.0	4.8156	.31136E-03	.38259E-03	.59031E-03	.52746E+00	1.3157	.8527
130.0	.64226	2436.9	2234.5	4.8108	.30632E-03	.37174E-03	.57213E-03	.53541E+00	1.3124	.8527
140.0	.64588	2443.9	2227.2	4.8060	.30159E-03	.36160E-03	.55520E-03	.54320E+00	1.3093	.8527
150.0	.64943	2451.1	2220.1	4.8014	.29712E-03	.35208E-03	.53938E-03	.55085E+00	1.3064	.8527
160.0	.65289	2458.3	2213.2	4.7969	.29289E-03	.34313E-03	.52456E-03	.55836E+00	1.3036	.8527
170.0	.65628	2465.5	2206.5	4.7924	.28889E-03	.33470E-03	.51064E-03	.56573E+00	1.3010	.8527
180.0	.65960	2472.9	2200.0	4.7881	.28508E-03	.32673E-03	.49753E-03	.57299E+00	1.2985	.8527
190.0	.66284	2480.3	2193.7	4.7838	.28146E-03	.31919E-03	.48516E-03	.58013E+00	1.2961	.8527
200.0	.66603	2487.8	2187.5	4.7796	.27800E-03	.31203E-03	.47345E-03	.58717E+00	1.2939	.8527
250.0	.68109	2525.9	2158.9	4.7595	.26276E-03	.28107E-03	.42319E-03	.62091E+00	1.2839	.8527
300.0	.69494	2565.1	2133.4	4.7409	.25016E-03	.25622E-03	.38330E-03	.65267E+00	1.2756	.8527
350.0	.70779	2604.9	2110.4	4.7235	.23945E-03	.23573E-03	.35068E-03	.68282E+00	1.2685	.8527
400.0	.71980	2645.4	2089.7	4.7070	.23017E-03	.21847E-03	.32342E-03	.71167E+00	1.2623	.8527
450.0	.73110	2686.3	2070.8	4.6915	.22196E-03	.20368E-03	.30019E-03	.73940E+00	1.2568	.8527
500.0	.74178	2727.5	2053.4	4.6766	.21463E-03	.19082E-03	.28012E-03	.76619E+00	1.2518	.8527
600.0	.76154	2810.7	2022.8	4.6489	.20197E-03	.16952E-03	.24710E-03	.81738E+00	1.2429	.8527

SUBCOOLED SODIUM LIQUID PROPERTIES AT T = 1900.0 DEG K

P (MPA)	MMOL (G/CC)	MLIQ (J/G)	ELIQ (J/G)	SLIQ (J/G-K)	ALPHAP (K-1)	BETAS (MPA-1)	BETAT (MPA-1)	GAMMAV (MPA/K)	CP (J/G-K)	CV (J/G-K)
.57047E+01	.55589	2519.7	2509.5	4.9667	.53647E-03	.73560E-03	.13655E-02	.39287E+00	1.5616	.8413
10.0	.55910	2519.7	2501.8	4.9626	.52122E-03	.71395E-03	.13114E-02	.39745E+00	1.5452	.8413
20.0	.56616	2520.4	2485.1	4.9536	.49011E-03	.66909E-03	.12023E-02	.40763E+00	1.5117	.8413
30.0	.57274	2522.1	2469.7	4.9453	.46388E-03	.63056E-03	.11118E-02	.41723E+00	1.4833	.8413
40.0	.57892	2524.5	2455.4	4.9374	.44138E-03	.59700E-03	.10353E-02	.42634E+00	1.4589	.8413
50.0	.58474	2527.6	2442.1	4.9300	.42180E-03	.56744E-03	.96960E-03	.43503E+00	1.4375	.8413
60.0	.59027	2531.3	2429.6	4.9230	.40457E-03	.54116E-03	.91255E-03	.44334E+00	1.4186	.8413
70.0	.59553	2535.4	2417.9	4.9163	.38925E-03	.51760E-03	.86246E-03	.45133E+00	1.4018	.8413
80.0	.60055	2540.0	2406.8	4.9099	.37552E-03	.49634E-03	.81808E-03	.45902E+00	1.3866	.8413
90.0	.60536	2544.9	2396.3	4.9038	.36311E-03	.47702E-03	.77846E-03	.46645E+00	1.3729	.8413
100.0	.60998	2550.2	2386.3	4.8979	.35184E-03	.45938E-03	.74283E-03	.47365E+00	1.3603	.8413
110.0	.61443	2555.8	2376.8	4.8922	.34153E-03	.44319E-03	.71060E-03	.48062E+00	1.3488	.8413
120.0	.61872	2561.6	2367.7	4.8868	.33206E-03	.42827E-03	.68128E-03	.48740E+00	1.3383	.8413
130.0	.62283	2567.8	2359.1	4.8815	.30780E-03	.40132E-03	.62272E-03	.49429E+00	1.3054	.8413
140.0	.62665	2574.5	2351.1	4.8766	.30274E-03	.38932E-03	.60269E-03	.50231E+00	1.3023	.8413
150.0	.63038	2581.4	2343.4	4.8719	.29800E-03	.37814E-03	.58411E-03	.51017E+00	1.2995	.8413
160.0	.63402	2588.3	2335.9	4.8672	.29353E-03	.36770E-03	.56681E-03	.51786E+00	1.2968	.8413
170.0	.63757	2595.3	2328.7	4.8626	.28932E-03	.35792E-03	.55065E-03	.52541E+00	1.2943	.8413
180.0	.64104	2602.4	2321.6	4.8581	.28533E-03	.34873E-03	.53552E-03	.53282E+00	1.2919	.8413
190.0	.64444	2609.6	2314.8	4.8537	.28155E-03	.34007E-03	.52130E-03	.54010E+00	1.2896	.8413
200.0	.64776	2616.9	2308.1	4.8494	.27796E-03	.33189E-03	.50792E-03	.54725E+00	1.2874	.8413
250.0	.66344	2654.0	2277.2	4.8288	.26227E-03	.29692E-03	.45106E-03	.58144E+00	1.2780	.8413
300.0	.67779	2692.3	2249.7	4.8097	.24943E-03	.26930E-03	.40660E-03	.61345E+00	1.2702	.8413
350.0	.69107	2731.5	2225.1	4.7919	.23860E-03	.24678E-03	.37065E-03	.64372E+00	1.2635	.8413
400.0	.70346	2771.4	2202.8	4.7751	.22925E-03	.22799E-03	.34085E-03	.67258E+00	1.2577	.8413
450.0	.71508	2811.7	2182.4	4.7593	.22103E-03	.21201E-03	.31565E-03	.70026E+00	1.2525	.8413
500.0	.72606	2852.5	2163.8	4.7442	.21373E-03	.19822E-03	.29402E-03	.72694E+00	1.2478	.8413
600.0	.74634	2934.8	2130.9	4.7161	.20115E-03	.17551E-03	.25861E-03	.77782E+00	1.2396	.8413

SUBCOOLED SODIUM LIQUID PROPERTIES AT T = 2000.0 DEG K

P (MPA)	RHOL (G/CC)	HLIQ (J/G)	ELIQ (J/G)	SLIQ (J/G-K)	ALPHAP (K-1)	BETAS (MPA-1)	BETAT (MPA-1)	GAMMAV (MPA/K)	CP (J/G-K)	CV (J/G-K)
.77939E+01	.52621	2680.9	2666.1	5.0474	.63240E-03	.89257E-03	.17979E-02	.35174E+00	1.6790	.8335
10.0	.52827	2679.8	2660.9	5.0447	.61971E-03	.87492E-03	.17480E-02	.35452E+00	1.6653	.8335
20.0	.53705	2676.3	2639.1	5.0336	.57024E-03	.80463E-03	.15560E-02	.36649E+00	1.6118	.8335
30.0	.54504	2674.5	2619.4	5.0234	.53075E-03	.74683E-03	.14057E-02	.37757E+00	1.5689	.8335
40.0	.55241	2673.9	2601.5	5.0141	.49830E-03	.69823E-03	.12845E-02	.38793E+00	1.5334	.8335
50.0	.55927	2674.5	2585.1	5.0053	.47103E-03	.65666E-03	.11844E-02	.39769E+00	1.5034	.8335
60.0	.56569	2676.0	2569.9	4.9972	.44771E-03	.62059E-03	.11002E-02	.40694E+00	1.4777	.8335
70.0	.57173	2678.2	2555.7	4.9895	.42747E-03	.58892E-03	.10282E-02	.41575E+00	1.4552	.8335
80.0	.57746	2681.0	2542.5	4.9822	.40969E-03	.56085E-03	.96583E-03	.42418E+00	1.4354	.8335
90.0	.58290	2684.4	2530.0	4.9753	.39391E-03	.53574E-03	.91126E-03	.43227E+00	1.4177	.8335
100.0	.58809	2688.3	2518.2	4.9687	.37978E-03	.51314E-03	.86304E-03	.44005E+00	1.4019	.8335
110.0	.59306	2692.6	2507.1	4.9624	.36704E-03	.49264E-03	.82008E-03	.44757E+00	1.3875	.8335
120.0	.59782	2697.2	2496.5	4.9563	.35548E-03	.47397E-03	.78155E-03	.45484E+00	1.3744	.8335
130.0	.60241	2702.2	2486.4	4.9505	.34492E-03	.45686E-03	.74676E-03	.46188E+00	1.3624	.8335
140.0	.60683	2707.5	2476.8	4.9448	.33522E-03	.44111E-03	.71518E-03	.46873E+00	1.3514	.8335
150.0	.61109	2713.1	2467.6	4.9394	.32628E-03	.42656E-03	.68636E-03	.47538E+00	1.3412	.8335
160.0	.61522	2718.9	2458.8	4.9341	.31801E-03	.41307E-03	.65995E-03	.48187E+00	1.3317	.8335
170.0	.61922	2724.9	2450.3	4.9291	.31031E-03	.40052E-03	.63564E-03	.48819E+00	1.3228	.8335
180.0	.62303	2731.3	2442.4	4.9242	.28446E-03	.37290E-03	.61500E-03	.49471E+00	1.2853	.8335
190.0	.62657	2738.2	2435.0	4.9197	.28056E-03	.36293E-03	.60873E-03	.50214E+00	1.2832	.8335
200.0	.63004	2745.3	2427.8	4.9152	.27687E-03	.35356E-03	.60448E-03	.50943E+00	1.2813	.8335
250.0	.64631	2781.5	2394.7	4.8942	.26087E-03	.31398E-03	.47945E-03	.54411E+00	1.2728	.8335
300.0	.66114	2819.1	2365.4	4.8748	.24792E-03	.28324E-03	.43013E-03	.57636E+00	1.2658	.8335
350.0	.67482	2857.7	2339.0	4.8566	.23707E-03	.25849E-03	.39070E-03	.60677E+00	1.2598	.8335
400.0	.68756	2897.0	2315.2	4.8396	.22775E-03	.23803E-03	.35829E-03	.63565E+00	1.2546	.8335
450.0	.69950	2936.8	2293.5	4.8235	.21959E-03	.22076E-03	.33106E-03	.66329E+00	1.2500	.8335
500.0	.71075	2977.1	2273.6	4.8081	.21234E-03	.20595E-03	.30777E-03	.68987E+00	1.2457	.8335
600.0	.73152	3058.7	2238.5	4.7796	.19991E-03	.18175E-03	.26999E-03	.74044E+00	1.2382	.8335

SUBCOOLED SODIUM LIQUID PROPERTIES AT T = 2100.0 DEG K

P (MPA)	RHOL (G/CC)	MLIQ (J/G)	ELIQ (J/G)	SLIQ (J/G-K)	ALPHAP (K-1)	BETAS (MPA-1)	BETAT (MPA-1)	GAMMAV (MPA/K)	CP (J/G-K)	CV (J/G-K)
.10336E+02	.49340	2854.6	2833.6	5.1296	.77346E-03	.11274E-02	.25030E-02	.30902E+00	1.8510	.8337
20.0	.50451	2844.3	2804.7	5.1155	.68811E-03	.10091E-02	.21293E-02	.32316E+00	1.7593	.8337
30.0	.51462	2837.0	2778.7	5.1027	.62339E-03	.91483E-03	.18536E-02	.33632E+00	1.6893	.8337
40.0	.52368	2832.1	2755.7	5.0912	.57362E-03	.83468E-03	.16467E-02	.34835E+00	1.6350	.8337
50.0	.53193	2829.0	2735.0	5.0807	.53386E-03	.77801E-03	.14850E-02	.35949E+00	1.5914	.8337
60.0	.53953	2827.4	2716.2	5.0711	.50117E-03	.72627E-03	.13548E-02	.36991E+00	1.5553	.8337
70.0	.54658	2827.0	2698.9	5.0621	.47368E-03	.68207E-03	.12474E-02	.37973E+00	1.5248	.8337
80.0	.55319	2827.5	2682.9	5.0537	.45017E-03	.64380E-03	.11572E-02	.38903E+00	1.4986	.8337
90.0	.55941	2828.9	2668.0	5.0458	.42976E-03	.61025E-03	.10801E-02	.39789E+00	1.4757	.8337
100.0	.56529	2831.0	2654.1	5.0383	.41183E-03	.58054E-03	.10135E-02	.40637E+00	1.4554	.8337
110.0	.57088	2833.7	2641.0	5.0312	.39592E-03	.55403E-03	.95519E-03	.41450E+00	1.4374	.8337
120.0	.57620	2836.9	2628.6	5.0244	.38168E-03	.53018E-03	.90376E-03	.42233E+00	1.4212	.8337
130.0	.58130	2840.5	2616.9	5.0179	.36884E-03	.50859E-03	.85801E-03	.42988E+00	1.4065	.8337
140.0	.58619	2844.6	2605.8	5.0117	.35718E-03	.48893E-03	.81700E-03	.43719E+00	1.3932	.8337
150.0	.59088	2849.1	2595.2	5.0057	.34654E-03	.47094E-03	.78002E-03	.44427E+00	1.3809	.8337
160.0	.59541	2853.8	2585.1	5.0000	.33677E-03	.45441E-03	.74647E-03	.45115E+00	1.3696	.8337
170.0	.59978	2858.9	2575.4	4.9944	.32776E-03	.43915E-03	.71590E-03	.45783E+00	1.3591	.8337
180.0	.60400	2864.2	2566.2	4.9891	.31942E-03	.42501E-03	.68790E-03	.46435E+00	1.3494	.8337
190.0	.60809	2869.8	2557.3	4.9838	.31167E-03	.41187E-03	.66215E-03	.47070E+00	1.3404	.8337
200.0	.61206	2875.6	2548.8	4.9788	.30444E-03	.39962E-03	.63839E-03	.47690E+00	1.3319	.8337
250.0	.62973	2908.7	2511.7	4.9563	.25848E-03	.33290E-03	.50802E-03	.50880E+00	1.2723	.8337
300.0	.64502	2945.7	2480.6	4.9365	.24558E-03	.29862E-03	.45364E-03	.54134E+00	1.2666	.8337
350.0	.65908	2983.7	2452.6	4.9181	.23483E-03	.27137E-03	.41063E-03	.57187E+00	1.2616	.8337
400.0	.67215	3022.5	2427.4	4.9008	.22563E-03	.24905E-03	.37556E-03	.60078E+00	1.2572	.8337
450.0	.68437	3061.9	2404.4	4.8845	.21759E-03	.23036E-03	.34628E-03	.62837E+00	1.2533	.8337
500.0	.69588	3101.8	2383.3	4.8690	.21047E-03	.21443E-03	.32140E-03	.65485E+00	1.2497	.8337
600.0	.71710	3182.7	2345.9	4.8401	.19828E-03	.18459E-03	.28120E-03	.70512E+00	1.2432	.8337
700.0	.73635	3264.5	2313.8	4.8135	.18807E-03	.16840E-03	.24993E-03	.75250E+00	1.2374	.8337

SUBCOOLED SODIUM LIQUID PROPERTIES AT T = 2200.0 DEG K

P (MPA)	RHOL (G/CC)	HLIQ (J/G)	ELIQ (J/G)	SLIQ (J/G-K)	ALPHAP (K-1)	BETAS (MPA-1)	BETAT (MPA-1)	GAMMAV (MPA/K)	CP (J/G-K)	CV (J/G-K)
.13358E+02	.45620	3046.6	3017.3	5.2160	.10019E-02	.15171E-02	.37915E-02	.26424E+00	2.1282	.8516
20.0	.46684	3031.3	2988.4	5.2024	.88262E-03	.13570E-02	.31906E-02	.27664E+00	2.0022	.8516
30.0	.48044	3014.4	2951.9	5.1852	.76136E-03	.11816E-02	.25988E-02	.29297E+00	1.8729	.8516
40.0	.49206	3002.5	2921.2	5.1704	.67811E-03	.10535E-02	.22064E-02	.30734E+00	1.7834	.8516
50.0	.50230	2994.0	2894.5	5.1574	.61657E-03	.95490E-03	.19249E-02	.32031E+00	1.7166	.8516
60.0	.51149	2988.0	2870.7	5.1458	.56877E-03	.87600E-03	.17121E-02	.33222E+00	1.6643	.8516
70.0	.51988	2984.0	2849.4	5.1351	.53030E-03	.81112E-03	.15449E-02	.34326E+00	1.6219	.8516
80.0	.52760	2981.5	2829.9	5.1253	.49849E-03	.75661E-03	.14097E-02	.35362E+00	1.5866	.8516
90.0	.53478	2980.3	2812.0	5.1162	.47165E-03	.71004E-03	.12979E-02	.36338E+00	1.5566	.8516
100.0	.54151	2980.1	2795.4	5.1076	.44860E-03	.66969E-03	.12038E-02	.37265E+00	1.5307	.8516
110.0	.54784	2980.7	2779.9	5.0996	.42855E-03	.63432E-03	.11234E-02	.38149E+00	1.5081	.8516
120.0	.55383	2982.1	2765.4	5.0920	.41089E-03	.60302E-03	.10537E-02	.38994E+00	1.4880	.8516
130.0	.55952	2984.2	2751.8	5.0847	.39520E-03	.57509E-03	.99281E-03	.39806E+00	1.4701	.8516
140.0	.56495	2986.8	2738.9	5.0778	.38113E-03	.54997E-03	.93902E-03	.40588E+00	1.4539	.8516
150.0	.57014	2989.8	2726.8	5.0712	.36842E-03	.52724E-03	.89114E-03	.41343E+00	1.4393	.8516
160.0	.57512	2993.4	2715.2	5.0649	.35688E-03	.50656E-03	.84823E-03	.42073E+00	1.4259	.8516
170.0	.57990	2997.3	2704.2	5.0588	.34632E-03	.48765E-03	.80953E-03	.42781E+00	1.4136	.8516
180.0	.58451	3001.6	2693.6	5.0529	.33663E-03	.47027E-03	.77443E-03	.43468E+00	1.4023	.8516
190.0	.58896	3006.2	2683.6	5.0473	.32769E-03	.45425E-03	.74243E-03	.44137E+00	1.3918	.8516
200.0	.59326	3011.0	2673.9	5.0418	.31940E-03	.43940E-03	.71314E-03	.44788E+00	1.3820	.8516
250.0	.61291	3038.9	2631.0	5.0168	.28553E-03	.37894E-03	.59705E-03	.47823E+00	1.3417	.8516
300.0	.62947	3072.9	2596.3	4.9957	.24234E-03	.31672E-03	.47682E-03	.50824E+00	1.2820	.8516
350.0	.64388	3110.5	2566.9	4.9771	.23184E-03	.28656E-03	.43021E-03	.53889E+00	1.2784	.8516
400.0	.65724	3148.9	2540.3	4.9596	.22287E-03	.26211E-03	.39249E-03	.56783E+00	1.2752	.8516
450.0	.66972	3188.0	2516.1	4.9431	.21504E-03	.24178E-03	.36119E-03	.59537E+00	1.2721	.8516
500.0	.68147	3227.6	2493.8	4.9275	.20810E-03	.22455E-03	.33470E-03	.62176E+00	1.2693	.8516
600.0	.70309	3307.8	2454.4	4.8983	.19622E-03	.19680E-03	.29212E-03	.67172E+00	1.2640	.8516
700.0	.72269	3369.1	2420.5	4.8715	.18631E-03	.17531E-03	.25922E-03	.71871E+00	1.2592	.8516

SUBCOOLED SODIUM LIQUID PROPERTIES AT T = 2300.0 DEG K

P (MPA)	RMOL (G/CC)	HLIQ (J/G)	ELIQ (J/G)	SLIQ (J/G-K)	ALPHAP (K-1)	BETAS (MPA-1)	BETAT (MPA-1)	GAMMAV (MPA/K)	CP (J/G-K)	CV (J/G-K)
.16881E+02	.41216	3268.5	3227.5	5.3109	.14377E-02	.22902E-02	.66400E-02	.21653E+00	2.6519	.9147
20.0	.42014	3252.6	3205.0	5.3008	.12838E-02	.20950E-02	.57125E-02	.22473E+00	2.4941	.9147
30.0	.44061	3215.9	3147.9	5.2747	.99208E-03	.16781E-02	.40218E-02	.24668E+00	2.1922	.9147
40.0	.45651	3191.8	3104.2	5.2545	.83295E-03	.14219E-02	.31480E-02	.26460E+00	2.0251	.9147
50.0	.46975	3174.7	3068.3	5.2377	.72978E-03	.12442E-02	.26056E-02	.28008E+00	1.9155	.9147
60.0	.48120	3162.3	3037.6	5.2232	.65621E-03	.11121E-02	.22328E-02	.29389E+00	1.8365	.9147
70.0	.49136	3153.2	3010.7	5.2103	.60048E-03	.10091E-02	.19594E-02	.30646E+00	1.7761	.9147
80.0	.50054	3146.6	2986.7	5.1987	.55645E-03	.92611E-03	.17495E-02	.31806E+00	1.7279	.9147
90.0	.50893	3141.9	2965.0	5.1880	.52057E-03	.85752E-03	.15829E-02	.32887E+00	1.6884	.9147
100.0	.51669	3138.7	2945.2	5.1781	.49063E-03	.79971E-03	.14471E-02	.33904E+00	1.6551	.9147
110.0	.52392	3136.8	2926.9	5.1690	.46517E-03	.75020E-03	.13342E-02	.34866E+00	1.6267	.9147
120.0	.53069	3136.0	2909.9	5.1604	.44318E-03	.70723E-03	.12386E-02	.35780E+00	1.6019	.9147
130.0	.53706	3136.0	2894.0	5.1522	.42395E-03	.66953E-03	.11566E-02	.36654E+00	1.5801	.9147
140.0	.54313	3136.9	2879.1	5.1445	.40695E-03	.63614E-03	.10855E-02	.37491E+00	1.5608	.9147
150.0	.54888	3138.4	2865.1	5.1372	.39179E-03	.60632E-03	.10231E-02	.38295E+00	1.5434	.9147
160.0	.55437	3140.5	2851.8	5.1303	.37816E-03	.57951E-03	.96788E-03	.39071E+00	1.5277	.9147
170.0	.55962	3143.1	2839.3	5.1236	.36582E-03	.55524E-03	.91867E-03	.39820E+00	1.5134	.9147
180.0	.56466	3146.1	2827.3	5.1172	.35458E-03	.53317E-03	.87451E-03	.40546E+00	1.5003	.9147
190.0	.56951	3149.6	2815.9	5.1110	.34429E-03	.51298E-03	.83464E-03	.41250E+00	1.4882	.9147
200.0	.57417	3153.4	2805.1	5.1051	.33482E-03	.49443E-03	.79844E-03	.41934E+00	1.4771	.9147
250.0	.59532	3177.0	2757.1	5.0782	.29671E-03	.42031E-03	.65788E-03	.45101E+00	1.4317	.9147
300.0	.61366	3206.0	2717.1	5.0548	.26895E-03	.36707E-03	.56101E-03	.47941E+00	1.3979	.9147
350.0	.62924	3240.7	2684.5	5.0350	.22807E-03	.30707E-03	.44917E-03	.50775E+00	1.3380	.9147
400.0	.64286	3278.9	2656.7	5.0174	.21945E-03	.27992E-03	.40888E-03	.53670E+00	1.3361	.9147
450.0	.65558	3317.7	2631.3	5.0008	.21192E-03	.25752E-03	.37562E-03	.56420E+00	1.3342	.9147
500.0	.66752	3357.0	2608.0	4.9850	.20524E-03	.23864E-03	.34754E-03	.59048E+00	1.3322	.9147
600.0	.68951	3436.8	2566.6	4.9556	.19379E-03	.20844E-03	.30273E-03	.64013E+00	1.3285	.9147
700.0	.70943	3517.7	2531.0	4.9286	.18419E-03	.18519E-03	.26822E-03	.68672E+00	1.3248	.9147

SUBCOOLED SODIUM LIQUID PROPERTIES AT T = 2400.0 DEG K

P (MPA)	RHOL (G/CC)	HLIQ (J/G)	ELIQ (J/G)	SLIQ (J/G-K)	ALPHAP (K-1)	BETAS (MPA-1)	BETAT (MPA-1)	GAMMAV (MPA/K)	CP (J/G-K)	CV (J/G-K)
.20421E+02	.35505	3552.0	3493.0	5.4270	.26224E-02	.45610E-02	.16041E-01	.16348E+00	4.0495	1.1514
30.0	.39092	3465.3	3388.6	5.3808	.14704E-02	.29664E-02	.75163E-02	.19563E+00	2.9174	1.1514
40.0	.41523	3415.6	3319.3	5.3497	.10856E-02	.22494E-02	.49420E-02	.21966E+00	2.5297	1.1514
50.0	.43338	3383.7	3268.3	5.3266	.89215E-03	.18454E-02	.37362E-02	.23879E+00	2.3312	1.1514
60.0	.44816	3361.3	3227.4	5.3078	.77181E-03	.15793E-02	.30256E-02	.25510E+00	2.2058	1.1514
70.0	.46077	3344.9	3193.0	5.2918	.68817E-03	.13883E-02	.25532E-02	.26953E+00	2.1175	1.1514
80.0	.47185	3332.6	3163.0	5.2778	.62592E-03	.12434E-02	.22149E-02	.28259E+00	2.0511	1.1514
90.0	.48178	3323.3	3136.5	5.2652	.57737E-03	.11290E-02	.19598E-02	.29460E+00	1.9988	1.1514
100.0	.49080	3316.4	3112.6	5.2537	.53820E-03	.10361E-02	.17602E-02	.30576E+00	1.9561	1.1514
110.0	.49910	3311.3	3090.9	5.2432	.50577E-03	.95888E-03	.15994E-02	.31623E+00	1.9205	1.1514
120.0	.50680	3307.7	3070.9	5.2334	.47837E-03	.89356E-03	.14669E-02	.32612E+00	1.8902	1.1514
130.0	.51400	3305.4	3052.5	5.2243	.45485E-03	.83748E-03	.13557E-02	.33550E+00	1.8640	1.1514
140.0	.52076	3304.1	3035.2	5.2157	.43436E-03	.78873E-03	.12611E-02	.34445E+00	1.8409	1.1514
150.0	.52715	3303.7	3019.1	5.2076	.41633E-03	.74591E-03	.11794E-02	.35301E+00	1.8205	1.1514
160.0	.53321	3304.1	3004.0	5.1999	.40031E-03	.70797E-03	.11082E-02	.36123E+00	1.8023	1.1514
170.0	.53898	3305.1	2989.7	5.1925	.38594E-03	.67407E-03	.10455E-02	.36915E+00	1.7858	1.1514
180.0	.54449	3306.8	2976.2	5.1855	.37297E-03	.64359E-03	.98983E-03	.37680E+00	1.7709	1.1514
190.0	.54977	3309.0	2963.4	5.1788	.36119E-03	.61601E-03	.94011E-03	.38420E+00	1.7572	1.1514
200.0	.55483	3311.6	2951.1	5.1724	.35042E-03	.59093E-03	.89538E-03	.39137E+00	1.7447	1.1514
250.0	.57759	3330.4	2897.6	5.1434	.30780E-03	.49292E-03	.72528E-03	.42438E+00	1.6942	1.1514
300.0	.59712	3355.9	2853.5	5.1186	.27739E-03	.42471E-03	.61131E-03	.45376E+00	1.6573	1.1514
350.0	.61433	3385.9	2816.1	5.0967	.25430E-03	.37417E-03	.52928E-03	.48046E+00	1.6287	1.1514
400.0	.62903	3421.2	2785.3	5.0779	.21536E-03	.31167E-03	.42451E-03	.50731E+00	1.5683	1.1514
450.0	.64194	3459.9	2758.9	5.0613	.20823E-03	.28600E-03	.38941E-03	.53474E+00	1.5677	1.1514
500.0	.65407	3499.1	2734.7	5.0455	.20189E-03	.26448E-03	.35992E-03	.56092E+00	1.5669	1.1514
600.0	.67637	3578.6	2691.5	5.0160	.19096E-03	.23024E-03	.31292E-03	.61025E+00	1.5649	1.1514
700.0	.69657	3659.2	2654.2	4.9888	.18177E-03	.20405E-03	.27690E-03	.65644E+00	1.5625	1.1514
800.0	.71506	3740.4	2621.6	4.9637	.17384E-03	.18325E-03	.24827E-03	.70020E+00	1.5608	1.1514

SUBCOOLED SODIUM LIQUID PROPERTIES AT T = 2500.0 DEG K

P (MPA)	RMOL (G/CC)	MLIQ (J/G)	ELIQ (J/G)	SLIQ (J/G-K)	ALPHAP (K-1)	BETAS (MPA-1)	BETAT (MPA-1)	GAMMAV (MPA/K)	CP (J/G-K)	CV (J/G-K)
.25484E+02	.23853	4188.3	4081.5	5.6794	.41398E-01	.14650E+00	.52221E+00	.79275E-01	47.8072	13.4113
30.0	.31707	3932.9	3838.3	5.5710	.31883E-02	.19081E-01	.23860E-01	.13362E+00	16.7704	13.4113
40.0	.36478	3806.0	3696.4	5.5086	.15611E-02	.79905E-02	.90658E-02	.17182E+00	15.2497	13.4113
50.0	.39191	3745.2	3617.7	5.4737	.11369E-02	.52277E-02	.57834E-02	.19658E+00	14.8370	13.4113
60.0	.41163	3706.5	3560.8	5.4483	.92676E-03	.39303E-02	.42868E-02	.21619E+00	14.6276	13.4113
70.0	.42787	3679.3	3515.7	5.4279	.79739E-03	.31678E-02	.34241E-02	.23288E+00	14.4963	13.4113
80.0	.44145	3659.1	3477.9	5.4106	.70818E-03	.26629E-02	.28601E-02	.24761E+00	14.4044	13.4113
90.0	.45331	3643.8	3445.3	5.3955	.64219E-03	.23025E-02	.24612E-02	.26093E+00	14.3354	13.4113
100.0	.46388	3632.0	3416.5	5.3821	.59098E-03	.20317E-02	.21635E-02	.27316E+00	14.2813	13.4113
110.0	.47346	3623.0	3390.7	5.3700	.54983E-03	.18204E-02	.19325E-02	.28451E+00	14.2373	13.4113
120.0	.48223	3616.1	3367.2	5.3588	.51587E-03	.16506E-02	.17478E-02	.29516E+00	14.2007	13.4113
130.0	.49035	3610.9	3345.7	5.3485	.48728E-03	.15111E-02	.15966E-02	.30520E+00	14.1695	13.4113
140.0	.49792	3607.1	3325.9	5.3389	.46278E-03	.13944E-02	.14704E-02	.31473E+00	14.1426	13.4113
150.0	.50502	3604.5	3307.5	5.3299	.44150E-03	.12951E-02	.13634E-02	.32381E+00	14.1190	13.4113
160.0	.51171	3602.9	3290.2	5.3214	.42281E-03	.12096E-02	.12716E-02	.33250E+00	14.0981	13.4113
170.0	.51805	3602.2	3274.1	5.3133	.40622E-03	.11353E-02	.11918E-02	.34084E+00	14.0795	13.4113
180.0	.52407	3602.3	3258.8	5.3057	.39137E-03	.10699E-02	.11218E-02	.34887E+00	14.0627	13.4113
190.0	.52982	3603.0	3244.4	5.2984	.37799E-03	.10119E-02	.10599E-02	.35662E+00	14.0474	13.4113
200.0	.53531	3604.3	3230.7	5.2914	.36585E-03	.96024E-03	.10048E-02	.36411E+00	14.0334	13.4113
250.0	.55978	3617.8	3171.2	5.2603	.31854E-03	.76705E-03	.79947E-03	.39843E+00	13.9781	13.4113
300.0	.58055	3639.5	3122.7	5.2339	.28546E-03	.64060E-03	.66578E-03	.42876E+00	13.9384	13.4113
350.0	.59871	3666.5	3081.9	5.2108	.26069E-03	.55103E-03	.57144E-03	.45619E+00	13.9079	13.4113
400.0	.61493	3697.3	3046.8	5.1901	.24123E-03	.48405E-03	.50109E-03	.48141E+00	13.8835	13.4113
450.0	.62885	3733.3	3017.7	5.1724	.20398E-03	.39041E-03	.40238E-03	.50693E+00	13.8224	13.4113
500.0	.64112	3772.4	2992.5	5.1566	.19804E-03	.36052E-03	.37158E-03	.53298E+00	13.8229	13.4113
600.0	.66368	3851.8	2947.8	5.1270	.18776E-03	.31301E-03	.32262E-03	.58198E+00	13.8229	13.4113
700.0	.68411	3932.2	2909.0	5.0998	.17904E-03	.27673E-03	.28520E-03	.62777E+00	13.8221	13.4113
800.0	.70282	4013.2	2875.0	5.0746	.17148E-03	.24796E-03	.25552E-03	.67108E+00	13.8206	13.4113

APPENDIX D

Tabulation of Superheated-Vapor Sodium Properties

<u>Property</u>	<u>Symbol</u>	<u>Units</u>
Temperature	T	K
Pressure	P	MPa
Density	RHOV	g/cm ³
Enthalpy	HVAP	J/g
Internal Energy	EVAP	J/g
Entropy	SLIQ	J/g·K
Thermal-Expansion Coefficient	ALPHAP	K ⁻¹
Adiabatic Compressibility	BETAS	MPa ⁻¹
Isothermal Compressibility	BETAT	MPa ⁻¹
Thermal Pressure Coefficient	GAMMAV	MPa/K
Constant-Pressure Specific Heat	CP	J/g·K
Constant-Volume Specific Heat	CV	J/g·K

SUPERHEATED SODIUM VAPOR PROPERTIES AT T = 400.0 DEG K

P (MPA)	RHOV (G/CC)	HVAP (J/G)	EVAP (J/G)	SVAP (J/G-K)	ALPHAP (K-1)	BETAS (MPA-1)	BETAT (MPA-1)	GAMMAV (MPA/K)	CP (J/G-K)	CV (J/G-K)
.10000E-09	.69163E-12	5020.7	4876.1	14.2746	.25264E-02	.62840E+10	.10004E+11	.25253E-12	.9919	.6230
.50000E-10	.34573E-12	5021.5	4876.8	14.5272	.25132E-02	.12298E+11	.20004E+11	.12563E-12	.9481	.5828
.20000E-10	.13027E-12	5021.9	4877.3	14.8597	.25053E-02	.30306E+11	.50004E+11	.50101E-13	.9217	.5580
.10000E-10	.69134E-13	5022.1	4877.4	15.1107	.25026E-02	.60310E+11	.10000E+12	.25025E-13	.9129	.5505

SUPERHEATED SODIUM VAPOR PROPERTIES AT T = 500.0 DEG K

P (MPA)	RHOV (G/CC)	HVAP (J/G)	EVAP (J/G)	SVAP (J/G-K)	ALPHAP (K-1)	BETAS (MPA-1)	BETAT (MPA-1)	GAMMAV (MPA/K)	CP (J/G-K)	CV (J/G-K)
.50000E-07	.27717E-09	5104.9	4924.5	12.2574	.20845E-02	.13431E+08	.20045E+08	.10399E-09	1.1842	.7435
.20000E-07	.11071E-09	5109.5	4928.9	12.5976	.20340E-02	.31680E+08	.50045E+08	.40643E-10	1.0171	.6438
.10000E-07	.55331E-10	5111.1	4930.4	12.8512	.20170E-02	.61784E+08	.10005E+09	.20161E-10	.9607	.5933
.50000E-08	.27659E-10	5111.9	4931.1	13.1034	.20085E-02	.12184E+09	.20005E+09	.10040E-10	.9325	.5679
.20000E-08	.11062E-10	5112.3	4931.5	13.4356	.20034E-02	.30188E+09	.50005E+09	.40065E-11	.9155	.5527
.10000E-08	.55307E-11	5112.5	4931.7	13.6866	.20017E-02	.60189E+09	.10000E+10	.20016E-11	.9098	.5476
.50000E-09	.27053E-11	5112.6	4931.8	13.9374	.20009E-02	.12019E+10	.20000E+10	.10004E-11	.9069	.5450
.20000E-09	.11061E-11	5112.6	4931.8	14.2689	.20003E-02	.30019E+10	.50000E+10	.40006E-12	.9052	.5435
.10000E-09	.55305E-12	5112.6	4931.8	14.5196	.20002E-02	.60020E+10	.10000E+11	.20002E-12	.9047	.5430
.50000E-10	.27052E-12	5112.7	4931.8	14.7702	.20001E-02	.12002E+11	.20000E+11	.10000E-12	.9044	.5427
.20000E-10	.11061E-12	5112.7	4931.8	15.1016	.20000E-02	.30002E+11	.50000E+11	.40001E-13	.9042	.5426
.10000E-10	.55305E-13	5112.7	4931.8	15.3523	.20000E-02	.60002E+11	.10000E+12	.20000E-13	.9042	.5425

SUPERHEATED SODIUM VAPOR PROPERTIES AT T = 600.0 DEG K

P (MPA)	RHOV (G/CC)	HVAP (J/G)	EVAP (J/G)	SVAP (J/G-K)	ALPHAP (K-1)	BETAS (MPA-1)	BETAT (MPA-1)	GAMHAV (MPA/K)	CP (J/G-K)	CV (J/G-K)
.20000E-05	.92574E-08	5188.7	4972.6	11.1132	.17749E-02	.34049E+06	.50209E+06	.35350E-08	1.2625	.8562
.10000E-05	.46187E-08	5195.8	4979.3	11.3750	.17214E-02	.64769E+06	.10021E+07	.17177E-08	1.0856	.7017
.50000E-06	.23069E-08	5199.4	4982.7	11.6313	.16942E-02	.12523E+07	.20021E+07	.84618E-09	.9954	.6227
.20000E-06	.92214E-09	5201.6	4984.7	11.9661	.16777E-02	.30556E+07	.50021E+07	.33540E-09	.9408	.5747
.10000E-06	.46097E-09	5202.3	4985.4	12.2179	.16722E-02	.60568E+07	.10002E+08	.16718E-09	.9225	.5586
.50000E-07	.23046E-09	5202.7	4985.8	12.4691	.16694E-02	.12056E+08	.20002E+08	.83463E-10	.9133	.5505
.20000E-07	.92178E-10	5202.9	4986.0	12.8008	.16678E-02	.30058E+08	.50002E+08	.33354E-10	.9078	.5457
.10000E-07	.46088E-10	5203.0	4986.0	13.0516	.16672E-02	.60059E+08	.10000E+09	.16672E-10	.9059	.5441
.50000E-08	.23044E-10	5203.0	4986.1	13.3023	.16669E-02	.12006E+09	.20000E+09	.83346E-11	.9050	.5433
.20000E-08	.92175E-11	5203.1	4986.1	13.6337	.16668E-02	.30006E+09	.50000E+09	.33335E-11	.9045	.5426
.10000E-08	.46087E-11	5203.1	4986.1	13.8844	.16667E-02	.60007E+09	.10000E+10	.16667E-11	.9043	.5426
.50000E-09	.23044E-11	5203.1	4986.1	14.1350	.16667E-02	.12001E+10	.20000E+10	.83335E-12	.9042	.5425
.20000E-09	.92174E-12	5203.1	4986.1	14.4664	.16667E-02	.30001E+10	.50000E+10	.33334E-12	.9041	.5425
.10000E-09	.46087E-12	5203.1	4986.1	14.7171	.16667E-02	.60001E+10	.10000E+11	.16667E-12	.9041	.5425
.50000E-10	.23044E-12	5203.1	4986.1	14.9677	.16667E-02	.12000E+11	.20000E+11	.83333E-13	.9041	.5425
.20000E-10	.92174E-13	5203.1	4986.1	15.2991	.16667E-02	.30000E+11	.50000E+11	.33333E-13	.9041	.5425
.10000E-10	.46087E-13	5203.1	4986.1	15.5498	.16667E-02	.60001E+11	.10000E+12	.16667E-13	.9041	.5425

SUPERHEATED SODIUM VAPOR PROPERTIES AT T = 760.0 DEG K

P (MPA)	KMOV (G/CM)	HVAP (J/G)	EVAP (J/G)	SVAP (J/G-K)	ALPHAP (K-1)	BETAS (MPA-1)	BETAT (MPA-1)	GAMMAV (MPA/K)	CP (J/G-K)	CV (J/G-K)
.50000E-04	.19987E-06	5254.3	5004.1	10.0851	.16427E-02	.14356E+05	.20226E+05	.81217E-07	1.6080	1.1413
.20000E-04	.79388E-07	5277.5	5025.5	10.4470	.15173E-02	.33296E+05	.50234E+05	.30204E-07	1.1977	.7939
.10000E-04	.39599E-07	5285.4	5032.9	10.7082	.14735E-02	.63802E+05	.10024E+06	.14700E-07	1.0530	.6703
.50000E-05	.19776E-07	5289.4	5036.6	10.9641	.14511E-02	.12412E+06	.20024E+06	.72471E-08	.9791	.6069
.20000E-05	.79045E-08	5291.9	5038.8	11.2987	.14376E-02	.30434E+06	.50024E+06	.28739E-08	.9342	.5684
.10000E-05	.39513E-08	5292.7	5039.6	11.5504	.14331E-02	.60442E+06	.10002E+07	.14328E-08	.9192	.5554
.50000E-06	.19754E-08	5293.1	5040.0	11.8016	.14308E-02	.12045E+07	.20002E+07	.71533E-09	.9117	.5490
.20000E-06	.79010E-09	5293.3	5040.2	12.1333	.14295E-02	.30045E+07	.50002E+07	.28588E-09	.9071	.5451
.10000E-06	.39504E-09	5293.4	5040.3	12.3841	.14290E-02	.60046E+07	.10000E+08	.14290E-09	.9056	.5438
.50000E-07	.19752E-09	5293.4	5040.3	12.6348	.14288E-02	.12005E+08	.20000E+08	.71439E-10	.9049	.5431
.20000E-07	.79007E-10	5293.5	5040.3	12.9662	.14287E-02	.30005E+08	.50000E+08	.28573E-10	.9044	.5427
.10000E-07	.39503E-10	5293.5	5040.3	13.2169	.14286E-02	.60005E+08	.10000E+09	.14286E-10	.9043	.5426
.50000E-08	.19752E-10	5293.5	5040.3	13.4676	.14286E-02	.12001E+09	.20000E+09	.71430E-11	.9042	.5425
.20000E-08	.79006E-11	5293.5	5040.3	13.7989	.14286E-02	.30001E+09	.50000E+09	.28572E-11	.9041	.5425
.10000E-08	.39503E-11	5293.5	5040.3	14.0496	.14286E-02	.60001E+09	.10000E+10	.14286E-11	.9041	.5425
.50000E-09	.19752E-11	5293.5	5040.3	14.3003	.14286E-02	.12000E+10	.20000E+10	.71429E-12	.9041	.5425
.20000E-09	.79006E-12	5293.5	5040.3	14.6316	.14286E-02	.30000E+10	.50000E+10	.28571E-12	.9041	.5425
.10000E-09	.39503E-12	5293.5	5040.3	14.8823	.14286E-02	.60001E+10	.10000E+11	.14286E-12	.9041	.5425
.50000E-10	.19752E-12	5293.5	5040.3	15.1330	.14286E-02	.12000E+11	.20000E+11	.71429E-13	.9041	.5425
.20000E-10	.79006E-13	5293.5	5040.3	15.4643	.14286E-02	.30000E+11	.50000E+11	.28571E-13	.9041	.5425
.10000E-10	.39503E-13	5293.5	5040.3	15.7150	.14286E-02	.60001E+11	.10000E+12	.14286E-13	.9041	.5425

SUPERHEATED SODIUM VAPOR PROPERTIES AT T = 600.0 DEG K

P (MPA)	HM0V (G/CC)	HVAP (J/G)	EVAP (J/G)	SVAP (J/G-K)	ALPHAP (K-1)	BETAS (MPA-1)	BETAT (MPA-1)	GAMMAV (MPA/K)	CP (J/G-K)	CV (J/G-K)
.50000E-03	.17671E-05	5310.7	5027.7	9.3615	.15507E-02	.14640E+04	.20415E+04	.75955E-06	1.8823	1.3498
.20000E-03	.69769E-06	5353.4	5066.8	9.7414	.13784E-02	.34042E+04	.50443E+04	.27326E-06	1.3275	.8959
.10000E-03	.34726E-06	5368.4	5080.5	10.0092	.13157E-02	.64913E+04	.10045E+05	.13097E-06	1.1216	.7248
.50000E-04	.17323E-06	5376.1	5087.5	10.2686	.12832E-02	.12551E+05	.20046E+05	.64014E-07	1.0144	.6351
.20000E-04	.69196E-07	5380.8	5091.7	10.6053	.12634E-02	.30594E+05	.50046E+05	.25244E-07	.9486	.5799
.10000E-04	.34582E-07	5382.3	5093.2	10.8578	.12567E-02	.60610E+05	.10005E+06	.12561E-07	.9264	.5612
.50000E-05	.17287E-07	5383.1	5093.9	11.1093	.12534E-02	.12062E+06	.20005E+06	.62653E-08	.9153	.5519
.20000E-05	.69137E-08	5383.6	5094.3	11.4412	.12513E-02	.30063E+06	.50005E+06	.25025E-08	.9086	.5462
.10000E-05	.34567E-08	5383.7	5094.4	11.6921	.12507E-02	.60063E+06	.10000E+07	.12506E-08	.9063	.5444
.50000E-06	.17283E-08	5383.8	5094.5	11.9428	.12503E-02	.12006E+07	.20000E+07	.62515E-09	.9052	.5434
.20000E-06	.69131E-09	5383.9	5094.6	12.2742	.12501E-02	.30007E+07	.50000E+07	.25002E-09	.9046	.5428
.10000E-06	.34565E-09	5383.9	5094.6	12.5249	.12501E-02	.60007E+07	.10000E+08	.12501E-09	.9043	.5427
.50000E-07	.17283E-09	5383.9	5094.6	12.7756	.12500E-02	.12001E+08	.20000E+08	.62502E-10	.9042	.5426
.20000E-07	.69131E-10	5383.9	5094.6	13.1070	.12500E-02	.30001E+08	.50000E+08	.25000E-10	.9042	.5425
.10000E-07	.34565E-10	5383.9	5094.6	13.3576	.12500E-02	.60002E+08	.10000E+09	.12500E-10	.9041	.5425
.50000E-08	.17283E-10	5383.9	5094.6	13.6083	.12500E-02	.12000E+09	.20000E+09	.62500E-11	.9041	.5425
.20000E-08	.69131E-11	5383.9	5094.6	13.9397	.12500E-02	.30001E+09	.50000E+09	.25000E-11	.9041	.5425
.10000E-08	.34565E-11	5383.9	5094.6	14.1903	.12500E-02	.60001E+09	.10000E+10	.12500E-11	.9041	.5425
.50000E-09	.17283E-11	5383.9	5094.6	14.4410	.12500E-02	.12000E+10	.20000E+10	.62500E-12	.9041	.5425
.20000E-09	.69131E-12	5383.9	5094.6	14.7724	.12500E-02	.30000E+10	.50000E+10	.25000E-12	.9041	.5425
.10000E-09	.34565E-12	5383.9	5094.6	15.0230	.12500E-02	.60001E+10	.10000E+11	.12500E-12	.9041	.5425
.50000E-10	.17283E-12	5383.9	5094.6	15.2737	.12500E-02	.12000E+11	.20000E+11	.62500E-13	.9041	.5425
.20000E-10	.69131E-13	5383.9	5094.6	15.6051	.12500E-02	.30000E+11	.50000E+11	.25000E-13	.9041	.5425
.10000E-10	.34565E-13	5383.9	5094.6	15.8557	.12500E-02	.60001E+11	.10000E+12	.12500E-13	.9041	.5425

SUPERHEATED SODIUM VAPOR PROPERTIES AT T = 900.0 DEG K

P (MPA)	HHOV (G/CC)	HVAP (J/G)	EVAP (J/G)	SVAP (J/G-K)	ALPHAP (K-1)	BETAS (MPA-1)	BETAT (MPA-1)	GAMMAV (MPA/K)	CP (J/G-K)	CV (J/G-K)
.20000E-02	.62978E-05	5393.5	5075.9	8.9847	.13726E-02	.35802E+03	.51145E+03	.26837E-05	1.7530	1.2271
.10000E-02	.31116E-05	5432.4	5111.0	9.2741	.12500E-02	.68015E+03	.10122E+04	.12349E-05	1.3603	.9141
.50000E-03	.15461E-05	5452.9	5129.6	9.5453	.11827E-02	.12991E+04	.20125E+04	.58768E-06	1.1409	.7364
.20000E-03	.61609E-06	5465.7	5141.0	9.8894	.11403E-02	.31155E+04	.50128E+04	.22748E-06	1.0010	.6221
.10000E-03	.30765E-06	5470.0	5144.9	10.1444	.11258E-02	.61223E+04	.10013E+05	.11244E-06	.9529	.5827
.50000E-04	.15372E-06	5472.1	5146.9	10.3972	.11185E-02	.12126E+05	.20013E+05	.55868E-07	.9286	.5627
.20000E-04	.61465E-07	5473.4	5148.0	10.7299	.11141E-02	.30129E+05	.50013E+05	.22276E-07	.9139	.5506
.10000E-04	.30729E-07	5473.9	5148.4	10.9810	.11126E-02	.60130E+05	.10001E+06	.11124E-07	.9090	.5465
.50000E-05	.15363E-07	5474.1	5148.6	11.2319	.11119E-02	.12013E+06	.20001E+06	.55589E-08	.9066	.5445
.20000E-05	.61451E-08	5474.2	5148.8	11.5635	.11114E-02	.30013E+06	.50001E+06	.22228E-08	.9051	.5433
.10000E-05	.30725E-08	5474.3	5148.8	11.8142	.11113E-02	.60014E+06	.10000E+07	.11112E-08	.9046	.5429
.50000E-06	.15362E-08	5474.3	5148.8	12.0649	.11112E-02	.12002E+07	.20000E+07	.55559E-09	.9044	.5427
.20000E-06	.61450E-09	5474.3	5148.8	12.3962	.11111E-02	.30002E+07	.50000E+07	.22223E-09	.9042	.5426
.10000E-06	.30725E-09	5474.3	5148.8	12.6469	.11111E-02	.60002E+07	.10000E+08	.11111E-09	.9042	.5425
.50000E-07	.15362E-09	5474.3	5148.8	12.8976	.11111E-02	.12000E+08	.20000E+08	.55556E-10	.9041	.5425
.20000E-07	.61449E-10	5474.3	5148.8	13.2290	.11111E-02	.30001E+08	.50000E+08	.22222E-10	.9041	.5425
.10000E-07	.30725E-10	5474.3	5148.8	13.4796	.11111E-02	.60001E+08	.10000E+09	.11111E-10	.9041	.5425
.50000E-08	.15362E-10	5474.3	5148.8	13.7303	.11111E-02	.12000E+09	.20000E+09	.55556E-11	.9041	.5425
.20000E-08	.61449E-11	5474.3	5148.8	14.0617	.11111E-02	.30000E+09	.50000E+09	.22222E-11	.9041	.5425
.10000E-08	.30725E-11	5474.3	5148.8	14.3123	.11111E-02	.60001E+09	.10000E+10	.11111E-11	.9041	.5425
.50000E-09	.15362E-11	5474.3	5148.8	14.5630	.11111E-02	.12000E+10	.20000E+10	.55556E-12	.9041	.5425
.20000E-09	.61449E-12	5474.3	5148.8	14.8944	.11111E-02	.30000E+10	.50000E+10	.22222E-12	.9041	.5425
.10000E-09	.30725E-12	5474.3	5148.8	15.1450	.11111E-02	.60001E+10	.10000E+11	.11111E-12	.9041	.5425
.50000E-10	.15362E-12	5474.3	5148.8	15.3957	.11111E-02	.12000E+11	.20000E+11	.55556E-13	.9041	.5425
.20000E-10	.61449E-13	5474.3	5148.8	15.7271	.11111E-02	.30000E+11	.50000E+11	.22222E-13	.9041	.5425
.10000E-10	.30725E-13	5474.3	5148.8	15.9777	.11111E-02	.60001E+11	.10000E+12	.11111E-13	.9041	.5425

SUPERHEATED SODIUM VAPOR PROPERTIES AT T = 1000.0 DEG K

P (MPA)	MMOV (G/CC)	HVAP (J/G)	EVAP (J/G)	SVAP (J/G-K)	ALPHAP (K-1)	BETAS (MPA-1)	BETAT (MPA-1)	GAMMAV (MPA/K)	CP (J/G-K)	CV (J/G-K)
.10000E-01	.28843E-04	5427.2	5080.5	8.4691	.13485E-02	.72521E+02	.10378E+03	.12994E-04	2.0150	1.4081
.50000E-02	.14136E-04	5491.6	5137.9	8.7764	.11927E-02	.13850E+03	.20417E+03	.58419E-05	1.5313	1.0388
.20000E-02	.55814E-05	5534.3	5176.0	9.1456	.10823E-02	.32598E+03	.50445E+03	.21455E-05	1.1755	.7596
.10000E-02	.27781E-05	5549.3	5189.3	9.4096	.10421E-02	.63003E+03	.10046E+04	.10374E-05	1.0435	.6545
.50000E-03	.13858E-05	5556.9	5196.2	9.6671	.10213E-02	.12326E+04	.20046E+04	.50947E-06	.9748	.5994
.20000E-03	.55350E-06	5561.6	5200.3	10.0026	.10086E-02	.30344E+04	.50046E+04	.20153E-06	.9326	.5655
.10000E-03	.27605E-06	5563.2	5201.7	10.2547	.10043E-02	.60350E+04	.10005E+05	.10038E-06	.9184	.5540
.50000E-04	.13829E-06	5563.9	5202.4	10.5060	.10022E-02	.12035E+05	.20005E+05	.50096E-07	.9113	.5482
.20000E-04	.55310E-07	5564.4	5202.8	10.8378	.10009E-02	.30036E+05	.50005E+05	.20015E-07	.9070	.5448
.10000E-04	.27654E-07	5564.6	5202.9	11.0886	.10004E-02	.60038E+05	.10000E+06	.10004E-07	.9055	.5430
.50000E-05	.13826E-07	5564.6	5203.0	11.3393	.10002E-02	.12004E+06	.20000E+06	.50010E-08	.9048	.5431
.20000E-05	.55305E-08	5564.7	5203.1	11.6711	.10001E-02	.30004E+06	.50000E+06	.20002E-08	.9044	.5427
.10000E-05	.27652E-08	5564.7	5203.1	11.9214	.10000E-02	.60005E+06	.10000E+07	.10000E-08	.9043	.5426
.50000E-06	.13826E-08	5564.7	5203.1	12.1725	.10000E-02	.12001E+07	.20000E+07	.50001E-09	.9042	.5425
.20000E-06	.55305E-09	5564.7	5203.1	12.5039	.10000E-02	.30001E+07	.50000E+07	.20000E-09	.9041	.5425
.10000E-06	.27652E-09	5564.7	5203.1	12.7545	.10000E-02	.60001E+07	.10000E+08	.10000E-09	.9041	.5425
.50000E-07	.13826E-09	5564.7	5203.1	13.0052	.10000E-02	.12000E+08	.20000E+08	.50000E-10	.9041	.5425
.20000E-07	.55304E-10	5564.7	5203.1	13.3366	.10000E-02	.30001E+08	.50000E+08	.20000E-10	.9041	.5425
.10000E-07	.27652E-10	5564.7	5203.1	13.5872	.10000E-02	.60001E+08	.10000E+09	.10000E-10	.9041	.5425
.50000E-08	.13826E-10	5564.7	5203.1	13.8379	.10000E-02	.12000E+09	.20000E+09	.50000E-11	.9041	.5425
.20000E-08	.55304E-11	5564.7	5203.1	14.1693	.10000E-02	.30000E+09	.50000E+09	.20000E-11	.9041	.5425
.10000E-08	.27652E-11	5564.7	5203.1	14.4199	.10000E-02	.60001E+09	.10000E+10	.10000E-11	.9041	.5425
.50000E-09	.13826E-11	5564.7	5203.1	14.6706	.10000E-02	.12000E+10	.20000E+10	.50000E-12	.9041	.5425
.20000E-09	.55304E-12	5564.7	5203.1	15.0020	.10000E-02	.30000E+10	.50000E+10	.20000E-12	.9041	.5425
.10000E-09	.27652E-12	5564.7	5203.1	15.2526	.10000E-02	.60001E+10	.10000E+11	.10000E-12	.9041	.5425
.50000E-10	.13826E-12	5564.7	5203.1	15.5033	.10000E-02	.12000E+11	.20000E+11	.50000E-13	.9041	.5425
.20000E-10	.55304E-13	5564.7	5203.1	15.8347	.10000E-02	.30000E+11	.50000E+11	.20000E-13	.9041	.5425
.10000E-10	.27652E-13	5564.7	5203.1	16.0853	.10000E-02	.60001E+11	.10000E+12	.10000E-13	.9041	.5425

SUPERHEATED SODIUM VAPOR PROPERTIES AT T = 1100.0 DEG K

P (MPA)	RHOV (G/CC)	HVAP (J/G)	EVAP (J/G)	SVAP (J/G-K)	ALPHAP (K-1)	BETAS (MPA-1)	BETAT (MPA-1)	GAMMAV (MPA/K)	CP (J/G-K)	CV (J/G-K)
.50000E-01	.13649E-03	5392.3	5025.9	7.8977	.14227E-02	.14757E+02	.21358E+02	.66610E-04	2.4682	1.7053
.20000E-01	.52173E-04	5534.1	5150.8	8.3397	.11656E-02	.35098E+02	.51683E+02	.22553E-04	1.7256	1.1720
.10000E-01	.25630E-04	5591.3	5201.1	8.6356	.10491E-02	.67145E+02	.10183E+03	.10302E-04	1.3610	.8974
.50000E-02	.12694E-04	5622.3	5228.4	8.9109	.98246E-03	.12895E+03	.20192E+03	.48655E-05	1.1459	.7318
.20000E-02	.50479E-05	5641.8	5245.6	9.2578	.93931E-03	.31056E+03	.50198E+03	.18712E-05	1.0043	.6213
.10000E-02	.25189E-05	5648.4	5251.4	9.5138	.92435E-03	.61124E+03	.10020E+04	.92251E-06	.9548	.5824
.50000E-03	.12582E-05	5651.8	5254.4	9.7671	.91676E-03	.12116E+04	.20020E+04	.45792E-06	.9296	.5626
.20000E-03	.50297E-06	5653.8	5256.1	10.1001	.91217E-03	.30119E+04	.50020E+04	.18236E-06	.9143	.5506
.10000E-03	.25144E-06	5654.4	5256.7	10.3513	.91063E-03	.60120E+04	.10002E+05	.91045E-07	.9092	.5465
.50000E-04	.12570E-06	5654.8	5257.0	10.6023	.90986E-03	.12012E+05	.20002E+05	.45488E-07	.9067	.5445
.20000E-04	.50279E-07	5655.0	5257.2	10.9338	.90940E-03	.30012E+05	.50002E+05	.18187E-07	.9051	.5433
.10000E-04	.25139E-07	5655.1	5257.3	11.1858	.90925E-03	.60013E+05	.10000E+06	.90923E-08	.9046	.5429
.50000E-05	.12569E-07	5655.1	5257.3	11.4365	.90917E-03	.12001E+06	.20000E+06	.45458E-08	.9044	.5427
.20000E-05	.50277E-08	5655.1	5257.3	11.7678	.90912E-03	.30002E+06	.50000E+06	.18182E-08	.9042	.5426
.10000E-05	.25138E-08	5655.1	5257.3	12.0185	.90911E-03	.60002E+06	.10000E+07	.90910E-09	.9042	.5425
.50000E-06	.12569E-08	5655.1	5257.3	12.2692	.90910E-03	.12000E+07	.20000E+07	.45455E-09	.9041	.5425
.20000E-06	.50277E-09	5655.1	5257.3	12.6005	.90909E-03	.30001E+07	.50000E+07	.18182E-09	.9041	.5425
.10000E-06	.25138E-09	5655.1	5257.3	12.8512	.90909E-03	.60001E+07	.10000E+08	.90909E-10	.9041	.5425
.50000E-07	.12569E-09	5655.1	5257.3	13.1019	.90909E-03	.12000E+08	.20000E+08	.45455E-10	.9041	.5425
.20000E-07	.50277E-10	5655.1	5257.3	13.4332	.90909E-03	.30000E+08	.50000E+08	.18182E-10	.9041	.5425
.10000E-07	.25138E-10	5655.1	5257.3	13.6839	.90909E-03	.60001E+08	.10000E+09	.90909E-11	.9041	.5425
.50000E-08	.12569E-10	5655.1	5257.3	13.9346	.90909E-03	.12000E+09	.20000E+09	.45455E-11	.9041	.5425
.20000E-08	.50277E-11	5655.1	5257.3	14.2659	.90909E-03	.30000E+09	.50000E+09	.18182E-11	.9041	.5425
.10000E-08	.25138E-11	5655.1	5257.3	14.5166	.90909E-03	.60001E+09	.10000E+10	.90909E-12	.9041	.5425
.50000E-09	.12569E-11	5655.1	5257.3	14.7673	.90909E-03	.12000E+10	.20000E+10	.45455E-12	.9041	.5425
.20000E-09	.50277E-12	5655.1	5257.3	15.0986	.90909E-03	.30000E+10	.50000E+10	.18182E-12	.9041	.5425
.10000E-09	.25138E-12	5655.1	5257.3	15.3493	.90909E-03	.60001E+10	.10000E+11	.90909E-13	.9041	.5425
.50000E-10	.12569E-12	5655.1	5257.3	15.6000	.90909E-03	.12000E+11	.20000E+11	.45455E-13	.9041	.5425

SUPERHEATED SODIUM VAPOR PROPERTIES AT T = 1200.0 DEG K

P (MPA)	RHOV (G/CC)	HVAP (J/G)	EVAP (J/G)	SVAP (J/G-K)	ALPHAP (K-1)	BETAS (MPA-1)	BETAT (MPA-1)	GAMMAV (MPA/K)	CP (J/G-K)	CV (J/G-K)
.10000E+00	.25028E-03	5462.5	5083.0	7.7504	.12698E-02	.72240E+01	.10691E+02	.11878E-03	2.2260	1.5055
.50000E-01	.12054E-03	5598.6	5183.8	8.0826	.10921E-02	.13932E+02	.20810E+02	.52478E-04	1.7250	1.1544
.20000E-01	.46964E-04	5682.0	5256.3	8.4736	.95059E-03	.32986E+02	.50915E+02	.18670E-04	1.2867	.8336
.10000E-01	.23272E-04	5712.8	5283.1	8.7464	.89474E-03	.63658E+02	.10096E+03	.88625E-05	1.1064	.6977
.50000E-02	.11579E-04	5729.0	5297.2	9.0087	.86478E-03	.12412E+03	.20098E+03	.43028E-05	1.0083	.6227
.20000E-02	.46180E-05	5738.8	5305.8	9.3473	.84610E-03	.30447E+03	.50100E+03	.16888E-05	.9465	.5752
.10000E-02	.23067E-05	5742.2	5308.7	9.6004	.83975E-03	.60460E+03	.10010E+04	.83891E-06	.9254	.5590
.50000E-03	.11528E-05	5743.9	5310.1	9.8522	.83655E-03	.12047E+04	.20010E+04	.41807E-06	.9148	.5507
.20000E-03	.46096E-06	5744.9	5311.0	10.1843	.83462E-03	.30047E+04	.50010E+04	.16689E-06	.9084	.5458
.10000E-03	.23046E-06	5745.2	5311.3	10.4352	.83398E-03	.60048E+04	.10001E+05	.83389E-07	.9062	.5441
.50000E-04	.11522E-06	5745.4	5311.4	10.6860	.83366E-03	.12005E+05	.20001E+05	.41681E-07	.9052	.5433
.20000E-04	.46088E-07	5745.5	5311.5	11.0175	.83346E-03	.30005E+05	.50001E+05	.16669E-07	.9045	.5428
.10000E-04	.23044E-07	5745.5	5311.5	11.2682	.83340E-03	.60006E+05	.10000E+06	.83339E-08	.9043	.5426
.50000E-05	.11522E-07	5745.5	5311.6	11.5219	.83337E-03	.12001E+06	.20000E+06	.41668E-08	.9042	.5426
.20000E-05	.46087E-08	5745.5	5311.6	11.8533	.83335E-03	.30001E+06	.50000E+06	.16667E-08	.9041	.5425
.10000E-05	.23044E-08	5745.5	5311.6	12.1040	.83334E-03	.60001E+06	.10000E+07	.83334E-09	.9041	.5425
.50000E-06	.11522E-08	5745.5	5311.6	12.3547	.83334E-03	.12000E+07	.20000E+07	.41667E-09	.9041	.5425
.20000E-06	.46087E-09	5745.5	5311.6	12.6860	.83333E-03	.30000E+07	.50000E+07	.16667E-09	.9041	.5425
.10000E-06	.23044E-09	5745.5	5311.6	12.9367	.83333E-03	.60001E+07	.10000E+08	.83333E-10	.9041	.5425
.50000E-07	.11522E-09	5745.5	5311.6	13.1874	.83333E-03	.12000E+08	.20000E+08	.41667E-10	.9041	.5425
.20000E-07	.46087E-10	5745.5	5311.6	13.5187	.83333E-03	.30000E+08	.50000E+08	.16667E-10	.9041	.5425
.10000E-07	.23044E-10	5745.5	5311.6	13.7694	.83333E-03	.60001E+08	.10000E+09	.83333E-11	.9041	.5425
.50000E-08	.11522E-10	5745.5	5311.6	14.0200	.83333E-03	.12000E+09	.20000E+09	.41667E-11	.9041	.5425
.20000E-08	.46087E-11	5745.5	5311.6	14.3514	.83333E-03	.30000E+09	.50000E+09	.16667E-11	.9041	.5425
.10000E-08	.23044E-11	5745.5	5311.6	14.6021	.83333E-03	.60001E+09	.10000E+10	.83333E-12	.9041	.5425
.50000E-09	.11522E-11	5745.5	5311.6	14.8527	.83333E-03	.12000E+10	.20000E+10	.41667E-12	.9041	.5425
.20000E-09	.46087E-12	5745.5	5311.6	15.1841	.83333E-03	.30000E+10	.50000E+10	.16667E-12	.9041	.5425
.10000E-09	.23044E-12	5745.5	5311.6	15.4348	.83333E-03	.60001E+10	.10000E+11	.83333E-13	.9041	.5425

SUPERHEATED SODIUM VAPOR PROPERTIES AT T = 1300.0 DEG K

P (MPA)	RHOV (G/CC)	HVAP (J/G)	EVAP (J/G)	SVAP (J/G-K)	ALPHAP (K-1)	BETAS (MPA-1)	BETAT (MPA-1)	GAMHAV (MPA/K)	CP (J/G-K)	CV (J/G-K)
.20000E+00	.46591E-03	5548.7	5119.5	7.5763	.11776E-02	.35619E+01	.53837E+01	.21873E-03	2.1222	1.4041
.10000E+00	.22354E-03	5674.9	5227.5	7.9075	.10103E-02	.68788E+01	.10444E+02	.96726E-04	1.6635	1.0956
.50000E-01	.10918E-03	5749.7	5291.8	8.2066	.90327E-03	.13235E+02	.20492E+02	.44080E-04	1.3381	.8642
.20000E-01	.43008E-04	5799.8	5334.8	8.5708	.82694E-03	.31640E+02	.50528E+02	.16366E-04	1.0941	.6851
.10000E-01	.21389E-04	5817.6	5350.1	8.8332	.79886E-03	.61843E+02	.10054E+03	.79455E-05	1.0022	.6164
.50000E-02	.10665E-04	5826.7	5357.9	9.0898	.78425E-03	.12197E+03	.20055E+03	.39105E-05	.9539	.5801
.20000E-02	.42589E-05	5832.2	5362.6	9.4249	.77529E-03	.30205E+03	.50055E+03	.15489E-05	.9242	.5577
.10000E-02	.21283E-05	5834.1	5364.2	9.6767	.77227E-03	.60208E+03	.10006E+04	.77184E-06	.9142	.5501
.50000E-03	.10638E-05	5835.0	5365.0	9.9280	.77075E-03	.12021E+04	.20006E+04	.38527E-06	.9092	.5463
.20000E-03	.42547E-06	5835.6	5365.5	10.2598	.76984E-03	.30021E+04	.50006E+04	.15395E-06	.9061	.5440
.10000E-03	.21272E-06	5835.8	5365.7	10.5105	.76954E-03	.60022E+04	.10001E+05	.76949E-07	.9051	.5432
.50000E-04	.10636E-06	5835.9	5365.7	10.7613	.76938E-03	.12002E+05	.20001E+05	.38468E-07	.9046	.5429
.20000E-04	.42542E-07	5835.9	5365.8	11.0990	.76929E-03	.30003E+05	.50001E+05	.15386E-07	.9043	.5426
.10000E-04	.21271E-07	5835.9	5365.8	11.3497	.76926E-03	.60003E+05	.10000E+06	.76926E-08	.9042	.5425
.50000E-05	.10636E-07	5835.9	5365.8	11.6004	.76925E-03	.12000E+06	.20000E+06	.38462E-08	.9042	.5425
.20000E-05	.42542E-08	5835.9	5365.8	11.9318	.76924E-03	.30001E+06	.50000E+06	.15385E-08	.9041	.5425
.10000E-05	.21271E-08	5835.9	5365.8	12.1824	.76923E-03	.60001E+06	.10000E+07	.76923E-09	.9041	.5425
.50000E-06	.10635E-08	5835.9	5365.8	12.4331	.76923E-03	.12000E+07	.20000E+07	.38462E-09	.9041	.5425
.20000E-06	.42542E-09	5835.9	5365.8	12.7645	.76923E-03	.30000E+07	.50000E+07	.15385E-09	.9041	.5425
.10000E-06	.21271E-09	5835.9	5365.8	13.0151	.76923E-03	.60001E+07	.10000E+08	.76923E-10	.9041	.5425
.50000E-07	.10635E-09	5835.9	5365.8	13.2658	.76923E-03	.12000E+08	.20000E+08	.38462E-10	.9041	.5425
.20000E-07	.42542E-10	5835.9	5365.8	13.5972	.76923E-03	.30000E+08	.50000E+08	.15385E-10	.9041	.5425
.10000E-07	.21271E-10	5835.9	5365.8	13.8478	.76923E-03	.60001E+08	.10000E+09	.76923E-11	.9041	.5425
.50000E-08	.10635E-10	5835.9	5365.8	14.0985	.76923E-03	.12000E+09	.20000E+09	.38462E-11	.9041	.5425
.20000E-08	.42542E-11	5835.9	5365.8	14.4299	.76923E-03	.30000E+09	.50000E+09	.15385E-11	.9041	.5425
.10000E-08	.21271E-11	5835.9	5365.8	14.6805	.76923E-03	.60001E+09	.10000E+10	.76923E-12	.9041	.5425
.50000E-09	.10635E-11	5835.9	5365.8	14.9312	.76923E-03	.12000E+10	.20000E+10	.38462E-12	.9041	.5425
.20000E-09	.42542E-12	5835.9	5365.8	15.2626	.76923E-03	.30000E+10	.50000E+10	.15385E-12	.9041	.5425

SUPERHEATED SODIUM VAPOR PROPERTIES AT T = 1400.0 DEG K

P (MPA)	RHOV (G/CC)	HVAP (J/G)	EVAP (J/G)	SVAP (J/G-K)	ALPHAP (K-1)	BETAS (MPA-1)	BETAT (MPA-1)	GAMMAV (MPA/K)	CP (J/G-K)	CV (J/G-K)
.50000E+00	.11200E-02	5526.1	5082.1	7.2650	.12073E-02	.14272E+01	.22246E+01	.54269E-03	2.2709	1.4569
.20000E+00	.41904E-03	5736.4	5259.1	7.7179	.95827E-03	.34176E+01	.52629E+01	.18208E-03	1.6617	1.0791
.10000E+00	.20380E-03	5823.8	5333.1	8.0203	.85088E-03	.65909E+01	.10291E+02	.82680E-04	1.3435	.8604
.50000E-01	.10037E-03	5872.8	5374.7	8.3003	.78744E-03	.12750E+02	.20311E+02	.38769E-04	1.1435	.7178
.20000E-01	.39766E-04	5904.3	5401.4	8.6506	.74492E-03	.30896E+02	.50325E+02	.14802E-04	1.0054	.6172
.10000E-01	.19818E-04	5915.2	5410.6	8.9079	.72985E-03	.60959E+02	.10033E+03	.72745E-05	.9557	.5807
.50000E-02	.98924E-05	5920.8	5415.3	9.1619	.72213E-03	.12100E+03	.20033E+03	.36047E-05	.9302	.5618
.20000E-02	.39530E-05	5924.1	5418.2	9.4953	.71744E-03	.30102E+03	.50033E+03	.14339E-05	.9146	.5503
.10000E-02	.19758E-05	5925.2	5419.1	9.7466	.71587E-03	.60103E+03	.10003E+04	.71563E-06	.9094	.5464
.50000E-03	.98775E-06	5925.8	5419.6	9.9976	.71508E-03	.12010E+04	.20003E+04	.35748E-06	.9067	.5444
.20000E-03	.39506E-06	5926.1	5419.9	10.3292	.71460E-03	.30011E+04	.50003E+04	.14291E-06	.9052	.5432
.10000E-03	.19752E-06	5926.2	5420.0	10.5799	.71444E-03	.60011E+04	.10000E+05	.71442E-07	.9046	.5429
.50000E-04	.98760E-07	5926.3	5420.0	10.8306	.71436E-03	.12001E+05	.20000E+05	.35718E-07	.9044	.5427
.20000E-04	.39503E-07	5926.3	5420.0	11.1733	.71432E-03	.30002E+05	.50000E+05	.14286E-07	.9042	.5425
.10000E-04	.19752E-07	5926.3	5420.1	11.4239	.71430E-03	.60002E+05	.10000E+06	.71430E-08	.9042	.5425
.50000E-05	.98758E-08	5926.4	5420.1	11.6746	.71429E-03	.12000E+06	.20000E+06	.35715E-08	.9041	.5425
.20000E-05	.39503E-08	5926.4	5420.1	12.0060	.71429E-03	.30000E+06	.50000E+06	.14286E-08	.9041	.5425
.10000E-05	.19752E-08	5926.4	5420.1	12.2566	.71429E-03	.60001E+06	.10000E+07	.71429E-09	.9041	.5425
.50000E-06	.98758E-09	5926.4	5420.1	12.5073	.71429E-03	.12000E+07	.20000E+07	.35714E-09	.9041	.5425
.20000E-06	.39503E-09	5926.4	5420.1	12.8387	.71429E-03	.30000E+07	.50000E+07	.14286E-09	.9041	.5425
.10000E-06	.19752E-09	5926.4	5420.1	13.0893	.71429E-03	.60001E+07	.10000E+08	.71429E-10	.9041	.5425
.50000E-07	.98758E-10	5926.4	5420.1	13.3400	.71429E-03	.12000E+08	.20000E+08	.35714E-10	.9041	.5425
.20000E-07	.39503E-10	5926.4	5420.1	13.6714	.71429E-03	.30000E+08	.50000E+08	.14286E-10	.9041	.5425
.10000E-07	.19752E-10	5926.4	5420.1	13.9220	.71429E-03	.60001E+08	.10000E+09	.71429E-11	.9041	.5425
.50000E-08	.98758E-11	5926.4	5420.1	14.1727	.71429E-03	.12000E+09	.20000E+09	.35714E-11	.9041	.5425
.20000E-08	.39503E-11	5926.4	5420.1	14.5041	.71429E-03	.30000E+09	.50000E+09	.14286E-11	.9041	.5425
.10000E-08	.19752E-11	5926.4	5420.1	14.7547	.71429E-03	.60001E+09	.10000E+10	.71429E-12	.9041	.5425
.50000E-09	.98758E-12	5926.4	5420.1	15.0054	.71429E-03	.12000E+10	.20000E+10	.35714E-12	.9041	.5425

SUPERHEATED SODIUM VAPOR PROPERTIES AT T = 1500.0 DEG K

P (MPA)	MMOV (G/CC)	HVAP (J/G)	EVAP (J/G)	SVAP (J/G-K)	ALPHAP (K-1)	BETAS (MPA-1)	BETAT (MPA-1)	GAMHAV (MPA/K)	CP (J/G-K)	CV (J/G-K)
.10000E+01	.21849E-02	5518.9	5061.2	7.0460	.12247E-02	.71237E+00	.11540E+01	.10613E-02	2.3300	1.4384
.50000E+00	.10097E-02	5730.7	5235.5	7.4082	.98523E-03	.13795E+01	.21626E+01	.45558E-03	1.8402	1.1738
.20000E+00	.38364E-03	5887.3	5366.0	7.8240	.81572E-03	.32960E+01	.51833E+01	.15737E-03	1.3780	.8762
.10000E+00	.18820E-03	5948.6	5417.2	8.1083	.74737E-03	.63828E+01	.10197E+02	.73287E-04	1.1666	.7302
.50000E-01	.93156E-04	5981.7	5444.9	8.3773	.70890E-03	.12450E+02	.20206E+02	.35084E-04	1.0432	.6427
.20000E-01	.37029E-04	6002.5	5462.3	8.7202	.68408E-03	.30504E+02	.50212E+02	.13624E-04	.9618	.5843
.10000E-01	.18475E-04	6009.6	5468.3	8.9748	.67547E-03	.60525E+02	.10021E+03	.67402E-05	.9333	.5637
.50000E-02	.92274E-05	6013.2	5471.3	9.2275	.67109E-03	.12054E+03	.20022E+03	.33518E-05	.9188	.5532
.20000E-02	.36886E-05	6015.3	5473.1	9.5601	.66844E-03	.30055E+03	.50022E+03	.13363E-05	.9100	.5468
.10000E-02	.18439E-05	6016.0	5473.7	9.8111	.66756E-03	.60055E+03	.10002E+04	.66741E-06	.9071	.5446
.50000E-03	.92184E-06	6016.4	5474.0	10.0620	.66711E-03	.12000E+04	.20002E+04	.33352E-06	.9056	.5435
.20000E-03	.36871E-06	6016.6	5474.2	10.3935	.66684E-03	.30000E+04	.50002E+04	.13336E-06	.9047	.5429
.10000E-03	.18435E-06	6016.7	5474.3	10.6442	.66676E-03	.60000E+04	.10000E+05	.66674E-07	.9044	.5427
.50000E-04	.92175E-07	6016.7	5474.3	10.9126	.66671E-03	.12001E+05	.20000E+05	.33335E-07	.9042	.5426
.20000E-04	.36870E-07	6016.8	5474.3	11.2439	.66668E-03	.30001E+05	.50000E+05	.13334E-07	.9042	.5425
.10000E-04	.18435E-07	6016.8	5474.3	11.4946	.66668E-03	.60001E+05	.10000E+06	.66667E-08	.9041	.5425
.50000E-05	.92174E-08	6016.8	5474.3	11.7453	.66667E-03	.12000E+06	.20000E+06	.33334E-08	.9041	.5425
.20000E-05	.36870E-08	6016.8	5474.3	12.0766	.66667E-03	.30000E+06	.50000E+06	.13333E-08	.9041	.5425
.10000E-05	.18435E-08	6016.8	5474.3	12.3273	.66667E-03	.60001E+06	.10000E+07	.66667E-09	.9041	.5425
.50000E-06	.92174E-09	6016.8	5474.3	12.5780	.66667E-03	.12000E+07	.20000E+07	.33333E-09	.9041	.5425
.20000E-06	.36870E-09	6016.8	5474.3	12.9093	.66667E-03	.30000E+07	.50000E+07	.13333E-09	.9041	.5425
.10000E-06	.18435E-09	6016.8	5474.3	13.1600	.66667E-03	.60001E+07	.10000E+08	.66667E-10	.9041	.5425
.50000E-07	.92174E-10	6016.8	5474.3	13.4107	.66667E-03	.12000E+08	.20000E+08	.33333E-10	.9041	.5425
.20000E-07	.36870E-10	6016.8	5474.3	13.7420	.66667E-03	.30000E+08	.50000E+08	.13333E-10	.9041	.5425
.10000E-07	.18435E-10	6016.8	5474.3	13.9927	.66667E-03	.60001E+08	.10000E+09	.66667E-11	.9041	.5425
.50000E-08	.92174E-11	6016.8	5474.3	14.2434	.66667E-03	.12000E+09	.20000E+09	.33333E-11	.9041	.5425
.20000E-08	.36870E-11	6016.8	5474.3	14.5747	.66667E-03	.30000E+09	.50000E+09	.13333E-11	.9041	.5425
.10000E-08	.18435E-11	6016.8	5474.3	14.8254	.66667E-03	.60001E+09	.10000E+10	.66667E-12	.9041	.5425

SUPERHEATED SODIUM VAPOR PROPERTIES AT T = 1600.0 DEG K

P (MPA)	KHUV (G/CC)	HVAP (J/G)	EVAP (J/G)	SVAP (J/G-K)	ALPHAP (K-1)	BETAS (MPA-1)	BETAT (MPA-1)	GAMMAV (MPA/K)	CP (J/G-K)	CV (J/G-K)
.10000E+01	.19556E-02	5732.1	5220.8	7.1852	.10045E-02	.69137E+00	.11153E+01	.90066E-03	1.9462	1.2065
.50000E+00	.92235E-03	5899.0	5356.9	7.5183	.83385E-03	.13372E+01	.21194E+01	.39343E-03	1.5411	.9723
.20000E+00	.35540E-03	6016.0	5453.2	7.9086	.71903E-03	.32039E+01	.51312E+01	.14013E-03	1.2073	.7538
.10000E+00	.17532E-03	6059.8	5489.4	8.1816	.67476E-03	.62455E+01	.10138E+02	.66556E-04	1.0672	.6574
.50000E-01	.87045E-04	6083.0	5508.6	8.4442	.65070E-03	.12274E+02	.20143E+02	.32305E-04	.9890	.6027
.20000E-01	.34667E-04	6097.4	5520.5	8.7829	.63550E-03	.30295E+02	.50146E+02	.12673E-04	.9389	.5672
.10000E-01	.17308E-04	6102.3	5524.5	9.0361	.63029E-03	.60303E+02	.10015E+03	.62936E-05	.9217	.5550
.50000E-02	.86477E-05	6104.7	5526.5	9.2880	.62765E-03	.12031E+03	.20015E+03	.31360E-05	.9129	.5488
.20000E-02	.34576E-05	6106.2	5527.7	9.6201	.62606E-03	.30031E+03	.50015E+03	.12518E-05	.9076	.5450
.10000E-02	.17285E-05	6106.7	5528.2	9.8711	.62553E-03	.60032E+03	.10001E+04	.62544E-06	.9059	.5437
.50000E-03	.86420E-06	6106.9	5528.4	10.1219	.62527E-03	.12003E+04	.20001E+04	.31261E-06	.9050	.5431
.20000E-03	.34566E-06	6107.1	5528.5	10.4533	.62511E-03	.30003E+04	.50001E+04	.12502E-06	.9045	.5427
.10000E-03	.17283E-06	6107.1	5528.5	10.7040	.62505E-03	.60004E+04	.10000E+05	.62504E-07	.9043	.5426
.50000E-04	.86414E-07	6107.2	5528.5	10.9799	.62503E-03	.12000E+05	.20000E+05	.31251E-07	.9042	.5425
.20000E-04	.34565E-07	6107.2	5528.6	11.3113	.62501E-03	.30001E+05	.50000E+05	.12500E-07	.9041	.5425
.10000E-04	.17283E-07	6107.2	5528.6	11.5619	.62501E-03	.60001E+05	.10000E+06	.62500E-08	.9041	.5425
.50000E-05	.86413E-08	6107.2	5528.6	11.8126	.62500E-03	.12000E+06	.20000E+06	.31250E-08	.9041	.5425
.20000E-05	.34565E-08	6107.2	5528.6	12.1187	.62500E-03	.30000E+06	.50000E+06	.12500E-08	.9041	.5425
.10000E-05	.17283E-08	6107.2	5528.6	12.3946	.62500E-03	.60001E+06	.10000E+07	.62500E-09	.9041	.5425
.50000E-06	.86413E-09	6107.2	5528.6	12.6453	.62500E-03	.12000E+07	.20000E+07	.31250E-09	.9041	.5425
.20000E-06	.34565E-09	6107.2	5528.6	12.9767	.62500E-03	.30000E+07	.50000E+07	.12500E-09	.9041	.5425
.10000E-06	.17283E-09	6107.2	5528.6	13.2273	.62500E-03	.60001E+07	.10000E+08	.62500E-10	.9041	.5425
.50000E-07	.86413E-10	6107.2	5528.6	13.4780	.62500E-03	.12000E+08	.20000E+08	.31250E-10	.9041	.5425
.20000E-07	.34565E-10	6107.2	5528.6	13.8093	.62500E-03	.30000E+08	.50000E+08	.12500E-10	.9041	.5425
.10000E-07	.17283E-10	6107.2	5528.6	14.0600	.62500E-03	.60001E+08	.10000E+09	.62500E-11	.9041	.5425
.50000E-08	.86413E-11	6107.2	5528.6	14.3107	.62500E-03	.12000E+09	.20000E+09	.31250E-11	.9041	.5425
.20000E-08	.34565E-11	6107.2	5528.6	14.6420	.62500E-03	.30000E+09	.50000E+09	.12500E-11	.9041	.5425
.10000E-08	.17283E-11	6107.2	5528.6	14.8927	.62500E-03	.60001E+09	.10000E+10	.62500E-12	.9041	.5425

DISTRIBUTIONUC-79 (206)UC-79b (41)DOE/RL (2)

Manager
Chief Patent Attorney

DOE/FFTFPO (5)

Director

DOE/RRT-HQ (2)

Program Division Director

HEDL (40)

GR Armstrong	W/C-78	RD Peak	W/C-75
JK Bigelow	W/C-78	GE Russcher	W/C-78
JE Ecker	W/C-78	DE Simpson	W/C-80
GL Fox	W/E-10	DE Smith	W/FED-124
RL Gibby	W/C-14	DD Stepnewski	W/C-75
JW Hagan	W/C-78	LN Stewart	W/FED-124
JE Hanson	W/E-4	HR Sullivan	W/C-80
CH Lewis	W/FED-124	KK Tabb	W/FED-124
FJ Martin	W/FED-124	AE Waltar	W/C-80
TB McCall	W/C-75	DM Wells	W/C-78
LM McWethy	W/C-78	NP Wilburn	W/FED-125
LD O'Dell	W/FED-124	SC Yung	W/FED-124
MR Oren	W/C-78	Central Files	(10)
KG Paasch	W/FED-124	Publications Services	(2)
A. Padilla (2)	W/FED-124		