Keywords: Saltstone
thermal effects
durability
leaching
morphology

DE92 016471

WSRC-RP-90-599

DISTRIBUTION: L. Nelson, 773-43A
P. E. Lowe, 773-65A
W. L. Tamosaitis, 773A
C. A. Langton, 773-43A
E. L. Wilhite, 773-43A
M. S. Hay, 773-43A
W. T. Goldston, 704S
H. Bull, III, 704Z
D.G. Thompson, 704Z
SRL Records(4), 773A

June 15, 1990

TO: W. E. Stevens, 773-43A

FROM: E. G. Orebaugh, 773-43A *eps*

TASK TECHNICAL AND QA PLAN

**THERMAL EFFECTS STUDY : TO EVALUATE SALTSTONE PROPERTIES
ASSOCIATED WITH PERFORMANCE CRITERIA AS A FUNCTION OF
EXTENDED EXPOSURE TO TEMPERATURES TYPICAL OF ADIABATIC
CURING.** (U)

Introduction:

This task involves extension of previous qualification studies for DWPF Saltstone formulations to evaluate the effect of exposure to temperatures typical of adiabatic curing for extended periods. Recent communications with Hanford's grouting group indicate severe performance deterioration of their saltstone (increased porosity and leachability) when subjected to extended exposure to temperatures typical of the adiabatic curing of their wastes. Prior experience at SRL with simulated Hanford salt wastes, demonstrated a much higher adiabatic maximum (chemical hydration heating) was to be expected with their wastes, than with SRS wastes. When these rapid chemical heats are combined with the long term radiolytic heating and thermal

JUN 18 1990

MASTER

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

yaz

isolation of their disposal vault scheme, Hanford expects high grout temperatures to extend well beyond the time of curing where chemical heat is evolved. Our saltstone, on the other hand, has consistently shown more moderate adiabatic heating, $<75^{\circ}\text{C}$, has no significant radiolytic thermal input. Nevertheless, centerline temperatures in the vault cells filled with grout can be expected to remain within the range of anticipated adiabatic temperatures for much longer periods than we have investigated previously.

Task Description

Requirements

At the request of L. Papouchado, WM WO, this task is being initiated to meet concerns of DOE, DWPF, and IWT to define the performance of DWPF saltstone subjected to conditions not previously tested. The criteria for performance will be the leach index obtained by conducting leach testing and computation according to the strict protocol established under ANS 16.1. The results of this study will add to the technical data base, providing reassurance to the future performance of this waste disposal scheme or suggest required modifications to attain desirable performance criteria.

Prerequisites

Since the study will involve only the testing of simulated DWPF saltstone, no notification of SCDHEC is required before testing can begin. Controlled procedures covering the unique curing of the grouts and the strict leaching procedures will be written and documented for use in this study. Any records necessary to qualify data generated by this study for inclusion in the basic data for the process will be kept in controlled laboratory notebooks and documented reports. All work and records will be performed and kept in accordance with QA guidelines.

Deliverables

Once the study is complete, a technical report documenting the results will be issued as a basis for future actions.

Task Activities

Saltstone grouts will be mixed from simulated waste salt solution (modified by the addition of 500 ppm dichromate ion, added as $\text{K}_2\text{Cr}_2\text{O}_7$) and the reference blend of solids consisting of Portland type II cement, ground slag, and flyash. Portions of the grout will be cast into polythene lined glass curing vials, (to obtain surface characteristics consistent with past studies), which will be positively sealed by glass fusion (to assure no water loss over the thermal exposure period), and placed in thermostatically controlled ovens ($\pm 5^{\circ}\text{C}$). Nine samples of grout will be treated initially in each of 4 ovens with mean temperatures of 25, 55, 75 and 95°C . After periods of 1, 2, 3, and 6 months, samples cured at each temperature will be removed, cooled, sectioned (to provide physical examination slices and leach specimens of required dimensions) and subjected to 90 days of leaching under the ANS 16.1 protocol. Other samples will be moved from their original curing ovens to other ovens at lower temperatures to simulate modeled cooling curves per(IWT-LLW-90-0241, A. D. Yu to W.E.Stevens, June 7, 1990) until such time as the modeling predicts a temperature of $<40^{\circ}\text{C}$, whereupon these samples will be cooled to ambient,

sectioned, examined, and leached the same as those held at constant temperature for different times. A second series of samples will be cured at varying temperatures but following a cooling curve that is twice as steep as that modeled by Yu. The remaining samples will serve as spares to be used as needed. The preparation and curing of these grouts will be carried out under a controlled procedure, see ref 3(draft). The leaching of these cured grouts under the protocols of ANS 16.1 is covered under a separate procedure written for this work, see ref. 4(draft). Since leaching data consists of several leachant changes and samplings over the 90 day test (which are integrated to produce the effective diffusion coefficient or index), it is felt that duplicate leach specimens will suffice to provide alternative data, should any one leachate analyze consistently to produce statistically improbable results due to inadvertent contamination.

The leachate will be assayed for sodium, nitrate, and chromate to provide the basis for the determination of the characteristic diffusion index for monovalent cations and anions and to evaluate the effectiveness of the slag as a chemical inhibitor to the migration of dichromate. Analysis of the leachate will be made by and under ADS methods: ICP#1500(sodium), IC#2306(nitrate), and ICP#1500(chromium). Since the analyses will be performed under these QA qualified procedures, no blind samples need be initiated by IWT; however, we will cooperate with ADS's quality control program to submit any blind standards supplied by them, as if they were routine leachate samples.

The only M&TE being used by IWT in the conduct of these studies will be a top loading electronic scale,(sensitivity 0.1 gram), laboratory thermometers to monitor/set oven temperatures, (minimum accuracy $\pm 1^{\circ}\text{C}$) and English scale calipers(self zeroing). The electronic scales are currently calibrated routinely. The thermometers will be calibrated/certified by the standards laboratory.

Physical examination of the sectioned slices will include as a minimum photomicrography and may be extended to include various measures of porosity and mineral speciation.

Preparation of the final report will compare the physical and chemical properties measured at the higher temperatures and exposures to those at 1 month and 25°C (which are typical of our past test conditions) to provide guidance for future operations of the grout production facilities.

Safety

Safety issues will be addressed in the two procedures written to impliment this task plan.

References

1. A. D. Yu to W.E.Stevens, IWT-LLW-90-0241, "Saltstone Vault Temperature Performance", June 7, 1990
2. American Nuclear Society, ANSI/ANS-16.1-1986, "Measurement of the leachability of low-level radioactive wastes by a short term test procedure", April 14, 1986
3. E. Orebaugh, IWT-XXXXXXX, "Preparation of saltstone and its curing in the study of thermal history during curing on the leach index".
4. E. Orebaugh, IWT XXXXXXXXX, "Leaching saltstone specimens to study the effects of thermal history during curing on performance."

W.E. Stevens 6/22/90
Level 4 Manager Approval

Paul E. Jones 7/24/90
Quality Section Review

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

END

**DATE
FILMED**

8 / 20 / 92