DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

QUARTERLY TECHNICAL PROGRESS REPORT 8
JULY - SEPTEMBER, 1988

ENHANCED DURABILITY AND REACTIVITY FOR
ZINC FERRITE DESULFURIZATION SORBENT

DOE/MC/23172--T12

DE92 017768

By
Mahesh C. Jha
Mark H. Berggren
AMAX Research & Development Center
5950 McIntyre Street
Golden, Colorado 80403-7499

Prepared for
U. S. Department of Energy
Morgantown Energy Technology Center
P. O. Box 880
3610 Collins Ferry Road
Morgantown, West Virginia 26507-0880

DOE Contract No. DE-AC21-86MC23172
AMAX Project No. 80270

November 14, 1988

MASTER

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

LEGAL NOTICE

THIS REPORT WAS PREPARED BY AMAX RESEARCH & DEVELOPMENT CENTER, AS AN ACCOUNT OF WORK SPONSORED BY MORGANTOWN ENERGY TECHNOLOGY CENTER. NEITHER AMAX RESEARCH & DEVELOPMENT CENTER NOR ANY PERSON ACTING ON ITS BEHALF:

- (A) MAKES ANY WARRANTY, EXPRESSED OR IMPLIED, WITH RESPECT TO THE USE OF ANY INFORMATION, APPARATUS, METHOD, OR PROCESS DISCLOSED IN THIS REPORT OR THAT SUCH USE MAY NOT INFRINGE PRIVATELY OWNED RIGHTS; OR
- (B) ASSUMES ANY LIABILITIES WITH RESPECT TO THE USE OF, OR FOR THE DAMAGES RESULTING FROM THE USE OF, ANY INFORMATION, APPARATUS, METHOD, OR PROCESS DISCLOSED IN THIS REPORT.

TABLE OF CONTENTS

	<u>Page</u>
SUMMARY	1
INTRODUCTION	2
ACCOMPLISHMENTS	3
TASK 1. EXPERIMENTAL TEST PLAN	3
TASK 2. SORBENT PREPARATION AND CHARACTERIZATION . .	3
Sorbent Preparation	3
Sorbent Characterization	3
TASK 3. BENCH-SCALE TESTING	10
Bench-Scale Test Results	10
Single Particle Kinetic Studies at LSU	15
TASK 4. BENCH-SCALE TEST ANALYSIS	21
TASK 5. TOPICAL REPORT	34

LIST OF TABLES

	<u>Page</u>
Table 1. Zinc Ferrite Spherical Pellet Characteristics	4
Table 2. Zinc Ferrite Cylindrical Extrude Characteristics	7
Table 3. Crush Strength Determinations for Spherical Pellet Sorbent P27A	9
Table 4. Surface Areas of Zinc Oxide and Iron Oxide Feedstocks	9
Table 5. Summary of Spherical Pellet Sorbent Performance	11
Table 6. Summary of Cylindrical Extrude Sorbent Performance	12
Table 7. Comparison of Sorbent Reactivity and Reactivity Maintenance	16
Table 8. Comparison of Pellet Reactivity	17
Table 9. Comparison of Extrude Reactivity	18
Table 10. Comparison of Pellet Reactivity Maintenance .	19
Table 11. Comparison of Extrude Reactivity Maintenance	20
Table 12. Chemical Analysis of Spherical Pellet Sorbents	21
Table 13. Chemical Analysis of Cylindrical Extrude Sorbents	22
Table 14. Physical Properties and Chemical Analyses of Fresh and Sulfided Sorbents	23
Table 15. Sulfur Sorption Capacity as a Function of Iron Oxide Grade	24
Table 16. Porosity of Fresh and Sulfided Sorbents . . .	28
Table 17. Zinc Ferrite Sorbent Grading System	30
Table 18. Zinc Ferrite Spherical Pellet Sorbent Performance Evaluation Criteria	32

LIST OF TABLES (Continued)

Table 19.	Zinc Ferrite Cylindrical Extrude Sorbent Performance Evaluation Criteria	33
Table 20.	Summary of Sorbent Performance	34

LIST OF FIGURES

Figure 1.	Spherical pellet crush strength as a function of sorbent bulk density.	13
Figure 2.	Attrition resistance as a function of sorbent bulk density.	13
Figure 3.	Spherical pellet attrition resistance as a function of crush strength.	14
Figure 4.	Cylindrical extrude attrition resistance as a function of crush strength.	14
Figure 5.	Surface area as a function of sorbent bulk density.	15
Figure 6.	Sulfur sorption capacity at 200 ppm H ₂ S breakthrough as a function of porosity contained in pores >0.18 μ m.	25
Figure 7.	Single particle reactivity as a function of porosity contained in pores >0.18 μ m.	25
Figure 8.	Average sulfur sorption capacity at 200 ppm H ₂ S breakthrough as a function of single particle reactivity.	26
Figure 9.	Calculated total porosity as a function of measured porosity (for pores >0.012 μ m).	27
Figure 10.	Sulfur sorption capacity at 200 ppm H ₂ S breakthrough as a function of fresh sorbent surface area.	29
Figure 11.	Sulfur sorption capacity at 200 ppm H ₂ S breakthrough as a function of sulfided sorbent surface area.	29

SUMMARY

AMAX Research & Development Center (AMAX R&D) has been investigating methods for improving the reactivity and durability of the zinc ferrite desulfurization sorbent. Zinc ferrite sorbents are intended for use in desulfurization of hot coal gas in integrated gasification combined cycle (IGCC) or molten carbonate fuel cell (MCFC) applications. The reactivity of the sorbent may be defined as its sulfur sorption capacity at the breakthrough point in a bench-scale, fixed-bed reactor. The durability may be defined as the ability of the sorbent to maintain its reactivity and other important physical characteristics such as size, strength, and specific surface area during 10 cycles of sulfidation and oxidation. Two base case sorbents, spherical pellets and cylindrical extrudes used in related METC sponsored projects, are being used to provide a basis for the comparison of physical characteristics and chemical reactivity.

During the eighth quarter of the project (July - September, 1988), cyclic bench-scale testing of sorbents prepared at AMAX R&D was completed and the sulfided sorbents were characterized. Characterization was also completed on a cylindrical extrude sorbent which was prepared using a low-cost iron oxide as one of the ingredients. Single particle kinetic studies were completed at Louisiana State University, and the final report was submitted to AMAX R&D. A sorbent grading system was utilized to rank sorbents on the basis of chemical reactivity factors, physical durability factors, and overall performance.

INTRODUCTION

The U. S. Department of Energy (DCE), through the Morgantown Energy Technology Center (METC), has been investigating a number of advanced systems for producing electric power from large coal reserves available in the United States. The integrated gasification combined cycle (IGCC) concept has been identified as one of the most promising technologies for coal utilization. The goal of hot gas cleanup programs at METC is to develop contaminant control technologies that operate under conditions compatible with those of the gasifier and power generator (gas turbine or molten carbonate fuel cell).

Sulfur control at high temperature and pressure forms a major portion of the hot gas cleanup program at METC. Previous research has established that high temperature desulfurization can be accomplished using solid zinc ferrite sorbents to remove sulfur species from the coal gas to the 10 ppmv level or less, and the sorbent can be regenerated with air for reuse. The zinc ferrite sorbents experience chemical, physical, and thermal changes during sulfidation and regeneration. Deterioration of sorbent performance and physical characteristics is strongly influenced by the chemical composition of the sorbent and the method of preparation.

The objective of the present contract is to systematically investigate methods for enhancing the physical durability and chemical reactivity of the zinc ferrite desulfurization sorbent.

The program is divided into the following five tasks:

- Task 1. Experimental Test Plan
- Task 2. Sorbent Preparation and Characterization
- Task 3. Bench-Scale Testing
- Task 4. Bench-Scale Analysis
- Task 5. Topical Report

Accomplishments for each of the major tasks are summarized in the following section.

ACCOMPLISHMENTS

TASK 1. EXPERIMENTAL TEST PLAN

No changes were made to the experimental test plan during the reporting period.

TASK 2. SORBENT PREPARATION AND CHARACTERIZATION

Sorbent Preparation

All of the sorbent formulations from the screening test matrix have been prepared. Sorbent preparation activity was limited to the evaluation of techniques required to remove chlorine from Ruthner-process iron oxide. In one test, the iron oxide was subjected to a mild caustic washing step. The total chlorine content was reduced from 0.49 percent in the feed to less than 70 ppm in the washed and filtered product. An additional test was performed to determine the degree of chlorine removal via heat treatment. For this test, the Ruthner iron oxide was heated to 1,500°F and held for 4 hours (similar to induration conditions which have been used to fire formed sorbent shapes). The resulting product contained 200 ppm Chlorine. These results indicate that effective chlorine removal could be achieved during a washing step and/or during sorbent firing at high temperature.

Sorbent Characterization

Tables 1 and 2 summarize the sorbent formulations and characteristics of the spherical pellet and cylindrical extrude shapes, respectively. Based on discussions with the COTR during a meeting at AMAX R&D, some of the units for reporting physical properties were changed. For example, loss on attrition values were converted to "attrition resistance", with values potentially ranging from 0 to 100 percent. Extrude crush strength values were converted to units of "pounds/mm (length)" from the "pounds" units previously used.

Consideration was given to reporting spherical pellet crush strength on the basis of "pounds/mm (diameter)". To evaluate the suitability of these units, a test was performed using relatively large and relatively small spherical pellets which were taken from the same sorbent batch. Sorbent P27A (Preparation Run No. 21, 1,900°F/4 hours) was selected since this sorbent exhibited fairly high crush strength and was fired for a 4-hour period, which ensures complete heat treatment throughout both larger and smaller pellets. Twenty small and twenty large spherical pellets were subjected to diameter and crush strength measurements. The results were averaged in terms of "pounds" and "pounds/mm (diameter)" values. As shown in Table 3, the larger-diameter pellets did exhibit greater average crush strength values expressed in "pounds" units.

Table 1. Zinc Ferrite Spherical Pellet Characteristics

Sorbent Sample Number	Run No.	Pellet Formulation			Induration Conditions Temp., Time, of Hours	Physical Properties			BET Surface Area, m ² /g	TGA Testing
		Fe ₂ O ₃ Grade	ZnO/ Fe ₂ O ₃	% Bentonite		Bulk Density, kg/L	Crush Strength, lb	Attrition Resistance, %		
1094-59	Base	Pigment	1.0	5	2	1.014	5.1	45.5	1.01	*
P1	2	Pigment	0.8	2	0	0.876	4.6	34.9		
P2					1,500 0.25	0.912	3.8	23.3		
P3					1,500 4.00	0.916	4.8	39.8		
P4					1,700 2.00	0.860	5.7	46.0		
P5					1,700 2.00	0.952	6.6	48.5	3.95	*
P6					1,900 0.25	1.529	40.3	89.8	1.28	*
P6A					1,900 4.00	1.488	22.0	89.0	1.68	
P7	3	Catalyst	1.0	2	0	0.999	9.3	57.2		
P8					1,500 0.25	0.952	6.8	59.3		
P9					1,500 4.00	1.013	10.0	66.3		
P10					1,700 2.00	1.048	10.1	68.4	2.43	*
P11					1,700 2.00	1.036	10.5	67.6	2.47	*
P11A					1,900 0.25	1.141	16.6	80.5	2.63	
P12					1,900 0.25	1.273	21.5	75.5	1.38	*
P13	5	Catalyst	0.8	2	2	1.028	14.5	83.8		
P14					1,500 0.25	1.034	17.6	81.3		
P15					1,500 4.00	1.075	18.2	86.2		
P16					1,700 2.00	1.196	27.3	89.3	1.55	*
P17					1,900 0.25	1.339	32.8	91.6	1.43	*
P18	19	Catalyst	1.0	10	0	0.956	10.2	63.5		
P19					1,500 0.25	0.955	11.3	66.5		
P20					1,500 4.00	0.952	11.6	68.0		
P21					1,700 2.00	0.955	12.3	70.3	2.46	*
P22					1,900 0.25	1.132	20.8	77.2	2.10	*
P22A					1,900 4.00	1.146	19.4	82.4		

Table 1. Zinc Ferrite Spherical Pellet Characteristics
(Continued)

Sorbent Sample Number	Pellet Formulation				Induration Conditions		Physical Properties			BET Surface Area, m ² /g	IGA Testing
	Run No.	Fe ₂ O ₃ Grade	ZnO/ Fe ₂ O ₃	Bentonite %	Temp., °F	Time, Hours	Bulk Density, kg/l	Crush Strength, lb	Attrition Resistance, %		
P23	21	Catalyst	0.8	10	2	1,500 0.25	0.914	5.7	57.6		
P24						1,500 4.00	0.902	7.1	61.0		
P25						1,700 2.00	0.922	10.4	65.0		
P26						1,900 0.25	0.956	15.0	74.5	2.05	*
P27						1,900 4.00	1.111	21.2	80.1	1.91	*
P27A						1,900 4.00	1.143	22.0	80.9	1.21	
P28	8	Pigment	1.0	2	2	1,500 0.25	0.900				
P29						1,500 4.00	0.918	3.7			
P30						1,700 2.00	0.906	3.9			
P31						1,900 0.25	0.972	6.5		2.57	*
P32						1,900 4.00	1.270	19.4			
P32A						1,900 4.00	1.276	20.5	74.9	0.77	*
P33	10	Pigment	0.8	5	0	1,500 0.25	0.878				
P34						1,500 4.00	0.834	4.3			
P35						1,700 2.00	0.877	5.2			
P36						1,900 0.25	0.993	10.0	50.1		
P37						1,900 4.00	1.456	34.8	89.2		
P37A						1,900 4.00	1.279	22.1	90.7	1.76	*
P38	16	Pigment	1.0	5	2	1,500 0.25	0.926				
P39						1,500 4.00	0.940	4.4			
P40						1,700 2.00	0.928	3.9			
P41						1,900 0.25	1.020	9.1	60.5		
P42						1,900 4.00	1.383	31.2	85.4		
P42A						1,900 4.00	1.240	17.0	79.1	1.07	*

Table 1. Zinc Ferrite Spherical Pellet Characteristics
(Continued)

Sorbent Sample Number	Run No.	Pellet Formulation				Induration		Physical Properties			BET Surface Area, m ² /g	TGA Testing
		Fe ₂ O ₃ Grade	ZnO/ Fe ₂ O ₃	% Bentonite	% Starch	Conditions		Bulk Density, kg/l	Crush Strength, lb	Attrition Resistance %		
						Temp., °F	Time, Hours					
P43	11	Catalyst	1.0	5	0	1,500	0.25	0.930	5.8			
P44						1,500	4.00	0.939	5.1			
P45						1,700	2.00	0.979	6.9			
P46						1,900	0.25	0.988	6.8			
P47						1,900	4.00	1.234	17.7	78.0	1.40	*
P48	13	Catalyst	0.8	5	2	1,500	0.25	0.889	7.3			
P49						1,500	4.00	0.882	5.7			
P50						1,700	2.00	0.920	9.0			
P51						1,900	0.25	0.997	13.4	67.3	1.76	*
P52						1,900	4.00	1.142	22.3	74.5	1.63	
P53	18	Pigment	0.8	10	0	1,500	0.25	0.860	3.5			
P54						1,500	4.00	0.846	5.1			
P55						1,700	2.00	0.858	5.6			
P56						1,900	0.25	0.860	5.8			
P57						1,900	4.00	1.275	45.3	84.9	1.67	*
P58	24	Pigment	1.0	10	2	1,500	0.25	0.712	0.6			
P59						1,500	4.00	0.733	0.8			
P60						1,700	2.00	0.751	1.8	20.4		
P61						1,900	0.25	0.729	2.2	15.5		
P62						1,900	4.00	0.947	12.2	50.8	1.64	*

Note: An "A" designation in the sorbent sample number indicates preparation of a larger sample for cyclic testing.

Table 2. Zinc Ferrite Cylindrical Extrude Characteristics

Sorbent Sample Number	Extrude Formulation					Induration		Physical Properties			BET Surface Area, m ² /g	TGA Testing
	Run No.	Fe ₂ O ₃ Grade	ZnO/ Fe ₂ O ₃	Bentonite % Methocel	Conditions		Bulk Density, kg/L	Crush Strength, lb/mm	Length, mm	Attrition Resistance %		
					Temp., °F	Time, Hours						
T-2465	Base	Catalyst	1.0	2	0		1.306	3.5	8.6	88.8	3.30	*
E1	1	Catalyst	0.8	2	0	1,500 0.25	1.199	2.6	11.1	90.2	5.12	*
E2						1,500 4.00	1.120	3.6	11.8	92.3	4.39	*
E2A						1,500 4.00	1.220	3.7	10.1	93.3		
E3						1,700 2.00	1.159	3.3	11.8	88.1		
E4						1,900 0.25	1.172	3.9	12.0	91.8	3.59	
E5						1,900 4.00	1.355	>5		94.3		
E6	4	Pigment	1.0	2	0	1,500 0.25	1.130	2.1	11.8	83.5		
E7						1,500 4.00	1.154	2.2	11.2	81.8	5.77	*
E7A						1,500 4.00	1.250	2.5	9.6	87.5	5.62	
E8						1,700 2.00	1.147	2.5	9.6	85.9		
E9						1,900 0.25	1.354	4.8	9.7	93.4	2.74	*
E10						1,900 4.00	1.501	>5		95.1		
E11	7	Catalyst	1.0	2	0.5	1,500 0.25	1.215	3.3	9.5	87.8	4.39	*
E12						1,500 4.00	1.196	3.2	10.4	86.7	4.36	*
E13						1,700 2.00	1.148	3.5	10.7	84.5	3.37	*
E13A						1,700 2.00	1.260	3.3	10.1	85.4	4.06	
E14						1,900 0.25	1.272	>5		91.7		
E15						1,900 4.00	1.623	>5		93.2	1.42	*
E16	9	Catalyst	0.8	5	0	1,500 0.25	1.269	>5		93.9	4.78	*
E17						1,500 4.00	1.238	>5		90.6		
E18						1,700 2.00	1.231	>5		89.2		
E19						1,900 0.25	1.367	>5		91.5	2.51	
E20						1,900 4.00	1.743	>5		94.3		

Table 2. Zinc Ferrite Cylindrical Extrude Characteristics
(Continued)

Sorbent Sample Number	Extrude Formulation				Induration		Physical Properties				BET Surface Area, m ² /g	TGA Testing
	Run No.	Fe ₂ O ₃ Grade	ZnO/ Fe ₂ O ₃	% Bentonite	% Methocel	Temp., °F	Time, Hours	Bulk Density, kg/l	Crush Strength, lb/mm	Length, mm	Attrition Resistance %	
E21	15	Catalyst	1.0	5	0.5	1,500	0.25	1.195	>5		90.1	*
E22						1,500	4.00	1.207	3.2	11.1	88.3	
E23						1,700	2.00	1.220	>5		89.8	
E24						1,900	0.25	1.300	>5		92.6	*
E24A						1,900	0.25	1.328	5.3	7.9	71.7	
E25						1,900	4.00	1.676	>5		94.7	
E26	14	Pigment	0.8	5	0.5	1,500	0.25	1.070	3.9	11.3	90.7	
E27						1,500	4.00	1.082	4.2	11.0	91.1	
E28						1,700	2.00	1.110	3.8	11.8	91.0	
E28A						1,700	2.00	1.115	3.3	9.0	87.3	*
E29						1,900	0.25	1.254	>5		94.0	
E30						1,900	4.00	1.888	>5		96.1	
E31	6	Pigment	0.8	2	0.5	1,500	0.25	1.168	2.8	9.3	86.1	*
E32						1,500	4.00	1.174	2.2	9.2	86.0	*
E32A						1,500	4.00	1.191	3.1	9.2	84.6	*
E33						1,700	2.00	1.123	2.9	8.9	87.5	
E34						1,900	0.25	1.234	4.1	9.4	91.0	*
E35						1,900	4.00	1.686	>5		97.1	*
E36	12	Pigment	1.0	5	0	1,500	0.25	1.092	3.9	10.2	93.1	*
E37						1,500	4.00	1.138	4.6	8.8	93.3	
E38						1,700	2.00	1.174	4.3	10.4	94.3	*
E39						1,900	0.25	1.314	>5		96.7	*
E40						1,900	4.00	2.039	>5		97.8	*

Note: An "A" designation in the sorbent sample number indicates preparation of a larger batch for cyclic testing.

However, the larger-diameter pellets exhibited lower average crush strength values in terms of "pounds/mm (diameter)". As a result of these measurements, all crush strength determinations for the spherical pellets were recorded as "pounds". These values should be valid for making comparisons between different sorbent batches, since the spherical pellets were screened to a narrow size range (near 5 mm) prior to introduction to the fixed-bed reactor.

Table 3. Crush Strength Determinations
for a Spherical Pellet Sorbent P27A

	Average Sorbent Diameter, mm	Crush Strength	
		lb	lb/mm (Diameter)
Small Pellets	4.3	23.0	5.4
Large Pellets	7.4	29.6	4.1

A cylindrical extrude sorbent prepared using the Ruthner iron oxide (0.49 percent chloride) exhibited a bulk density of about 0.77 kg/l and a crush strength of about 35 pounds. The surface area of this sorbent was 2.59 m²/g. A sample of the sorbent (called E7R) was forwarded to LSU for single particle kinetic studies using the TGA.

Surface area determinations were performed on the zinc oxide and on the various iron oxide feedstocks used for sorbent preparation. Table 4 summarizes the results. Although the Ruthner process iron oxide resulted in the greatest reactivity for any sorbent prepared and tested during the base program (as determined by TGA), this particular iron oxide exhibited the lowest surface area of the three potential feeds. The Mobay (Bayferrox) iron oxide exhibited the highest surface area of the three iron oxide feedstocks and has generally produced sorbents exhibiting the lowest reactivity. Thus, the surface area of the starting feed material is not a good indicator of the reactivity of the sorbent product.

Table 4. Surface Areas of Zinc
Oxide and Iron Oxide Feedstocks

Compound	Source	Surface Area, m ² /g
Fe ₂ O ₃	UCI	6.65
Fe ₂ O ₃	Mobay	9.75
Fe ₂ O ₃	Ruthner	2.21
ZnO	Asarco	7.59

Porosity determinations were made on the sorbents which were selected for bench-scale testing. Tables 5 and 6 summarize the porosity and other characteristics of these sorbents.

Relationships between the physical characteristics of spherical pellet and cylindrical extrude sorbents have been established using the program results. Statistical analysis of the data has so far been limited to linear and second order curve fitting. Figure 1 shows spherical pellet crush strength as a function of bulk density. The least-squares fit for the line shown in the figure provides a correlation coefficient of 0.80. No clear correlation between crush strength and bulk density was found for the cylindrical extrude shapes.

Figure 2 shows attrition resistance as a function of bulk density. In general, the cylindrical extrude sorbents exhibited greater values of both bulk density and attrition resistance compared to spherical pellets. Based on these results, sorbents with bulk density values greater than about 1.30 kg/l can be expected to exhibit attrition resistance values of greater than about 85 percent. Attrition resistance for spherical pellets drops rapidly as bulk density values decrease below about 1.10 kg/l.

Figure 3 shows the relationship between attrition resistance and crush strength for spherical pellets. This figure indicates that a constant value range of attrition resistance (above about 85 percent) occurs for crush strength values greater than about 25 pounds. Figure 4 shows the attrition resistance of cylindrical extrudes as a function of crush strength. A weaker relationship was found for this sorbent shape. However, fresh cylindrical extrude sorbent attrition resistance values greater than 81 percent were obtained regardless of crush strength.

Figure 5 shows the trend between bulk density and surface area values. In general, greater bulk density leads to lower surface area. Surface areas for cylindrical extrudes were observed to fall within a band of values greater than those for the spherical pellets.

TASK 3. BENCH-SCALE TESTING

Bench-Scale Test Results

Cyclic testing of sorbents E32A, E2A, and P22A was completed during the quarter. Multi-cycle bench-scale testing has been completed under the base contract. Summaries of the sorbent formulations selected for bench-scale testing and results of the multi-cycle tests are shown in Tables 5 and 6 for the spherical pellets and cylindrical extrude shapes, respectively.

Table 5. Summary of Spherical Pellet Sorbent Performance

<u>Sorbent Formulation</u>						
Sorbent Sample Number	1094-59	P11A	P6A	P27A	P37A	P22A
Preparation Run Number	—	3	2	21	10	19
Iron Oxide Grade	Pigment	Catalyst	Pigment	Catalyst	Pigment	Catalyst
ZnO/Fe ₂ O ₃ Ratio	1.0	1.0	0.8	0.8	0.8	1.0
Bentonite, %	5	2	2	10	5	10
Kaolin, %	1.5	—	—	—	—	—
Starch, %	2	0	0	2	0	0
Na ₂ CO ₃ , %	0.2	—	—	—	—	—
MoS ₂ , %	0.2	—	—	—	—	—
<u>Induration Conditions</u>						
Temperature, °F	1825	1900	1900	1900	1900	1900
Time, hours	3	0.25	4	4	4	4
<u>Physical Properties</u>						
Bulk Density, kg/l	1.014	1.141	1.488	1.143	1.389	1.146
Crush Strength, lb	5.1	16.6	22.0	22.0	22.1	19.4
Attrition Resistance, %	45.4	80.5	89.0	80.9	90.7	82.4
Surface Area, m ² /g	1.01	2.63	1.68	1.21	1.76	1.95
Total Pore Volume, cm ³ /g	0.277	0.319	0.207	0.270	0.212	0.296
Average Pore Radius, Å	5490	2430	2460	4460	2410	3040
Porosity, %, Pores >0.180 μm	48.5	59.7	49.1	52.7	48.8	56.8
Porosity, %, Pores >0.012 μm	59.2	63.8	52.1	56.2	52.3	59.6
Calculated Porosity ^a	64	66	56	61	55	59
<u>Cyclic Test Series Number</u>	5	7	9	11	14	17
<u>Desulfurization Performance in Bench-Scale Reactor</u>						
Sulfur Sorption Capacity, g S sorbed/100 g fresh sorbent						
a) At 200 ppm H ₂ S Breakthrough:						
1st Cycle	1.3	25.2	16.1	13.3	1.7	16.2
2nd Cycle	1.5	20.2	14.3	16.0	2.6	13.9
3rd Cycle	3.4	11.0 ^b	13.0	12.7	2.4	14.5
4th Cycle	1.4	34.2	10.4	9.8	2.1	12.8
5th Cycle	1.4	33.0	8.5	10.4	2.2	12.5
6th Cycle	1.2	24.8	6.8	7.5	3.3	14.3
7th Cycle	1.4	24.0	7.7	7.2	2.0	12.0
8th Cycle	0.8	19.5	7.0	7.0	3.3	12.1
9th Cycle	0.8	20.3	7.6	7.9	1.9	11.5
10th Cycle	1.3	21.0	8.0	7.7	2.8	14.2
Average	1.2	24.7	9.9	10.0	2.4	13.4
b) At Saturation, Actual ^c	33.7	32.6	27.1	29.5	27.6	31.0
c) At Saturation, Theoretical	37.3	39.1	39.1	35.9	37.9	35.9
Percent of Theoretical Capacity Achieved	90.4	83.4	69.6	82.2	72.8	86.4
<u>Desulfurization Performance in TGA</u>						
Sulfur Sorption Capacity During First Cycle at t = 20 minutes, g S sorbed/100 g fresh sorbent						
	21.7	28.2	20.8	25.6	17.8	25.3
Reactivity Change, Increase or Decrease in Reactivity During 2nd Cycle, %						
	6	-16	-10	-12	-27	-11

a From LSU calculations based on particle densities.

b Test cycle suspended early due to reactor system plugging.

c Based on weight percent S at bottom of reactor bed.

Table 6. Summary of Cylindrical Extrude Sorbent Performance

Sorbent Formulation

Sorbent Sample Number	T-2465	E13A	E7A	E24A	E28A	E32A	E2A
Run Number	--	7	4	15	14	6	1
Iron Oxide Grade	Catalyst	Catalyst	Pigment	Catalyst	Pigment	Pigment	Catalyst
ZnO/Fe ₂ O ₃ Ratio	1.0	1.0	1.0	1.0	0.8	0.8	0.8
Bentonite, %	2	2	2	5	5	2	2
Methocel, %	0	0.5	0	0.5	0.5	0.5	0

Induration Conditions

Temperature, °F	1550	1700	1500	1900	1700	1500	1500
Time, hours	2.4	2	4	0.5	2	4	4

Physical Properties

Bulk Density, kg/l	1.306	1.260	1.250	1.328	1.115	1.191	1.120
Crush Strength, lb/mm	3.5	4.4	2.5	5.3	3.3	3.1	3.7
Attrition Resistance, %	88.8	85.4	87.5	91.7	89.3	84.6	92.3
Surface Area, m ² /g	3.30	4.06	5.62	4.15	4.99	6.33	4.38
Total Pore Volume, cm ³ /g	0.256	0.239	0.265	0.249	0.250	0.279	0.263
Average Pore Radius, Å	1550	1180	940	1200	1000	880	1200
Porosity, %, Pores >0.180 µm	50.1	39.8	20.3	36.4	23.9	31.9	44.7
Porosity, %, Pores >0.012 µm	58.2	56.2	58.0	56.7	56.4	59.1	58.5
Calculated Porosity ^a	62	59	50	54	57	61	59

Cyclic Test Series Number	4	8	10	12	13	15	16
---------------------------	---	---	----	----	----	----	----

Desulfurization Performance

in Bench-Scale Reactor

Sulfur Sorption Capacity,
g S sorbed/100 g fresh sorbent

a) At 200 ppm H₂S Breakthrough:

1st Cycle	13.7	17.6	25.6	16.2	9.3	8.8	13.5
2nd Cycle	28.6	15.3	14.9	14.7	5.5	12.6	11.0
3rd Cycle	26.3	17.7	11.5	14.0	5.6	9.6	14.0
4th Cycle	24.0	17.1	10.8	12.2	6.0	9.6	10.0
5th Cycle	22.2	15.3	12.4	11.3	6.2	8.9	10.8
6th Cycle	22.6	20.3	10.4	11.0	5.7	9.0	13.1
7th Cycle	22.2	16.1	8.8	10.1	5.9	9.5	12.4
8th Cycle	20.2	15.8	8.8	9.6	5.8	8.4	12.3
9th Cycle	20.4	16.6	9.5	9.5	5.9	9.5	13.1
10th Cycle	22.3	25.3	9.2	9.8	5.8	15.2	15.1
Average	22.3	17.7	12.2	11.8	6.2	10.1	12.5

b) At Saturation, Actual ^b	34.3	36.9	35.4	37.3	32.7	37.4	39.6
---------------------------------------	------	------	------	------	------	------	------

c) At Saturation, Theoretical	39.1	39.1	39.1	37.9	37.9	39.1	39.1
-------------------------------	------	------	------	------	------	------	------

Percent of Theoretical Capacity Achieved	87.7	94.4	90.5	98.4	86.3	95.7	101.2
--	------	------	------	------	------	------	-------

Desulfurization Performance

in TGA

Sulfur Sorption Capacity During
First Cycle at t = 30 minutes,
g S sorbed/100 g fresh sorbent

	22.9	21.7	18.2	18.1	16.6	21.1	20.9
--	------	------	------	------	------	------	------

Reactivity Change, Increase or
Decrease in Reactivity
During 2nd Cycle, %

	-11	-24	-19	-40	-20	-9	-16
--	-----	-----	-----	-----	-----	----	-----

^a From LSU calculations based on particle densities.

^b Based on weight percent S at bottom of reactor bed.

Figure 1. Spherical pellet crush strength as a function of sorbent bulk density.

Figure 2. Attrition resistance as a function of sorbent bulk density.

Figure 3. Spherical pellet attrition resistance as a function of crush strength.

Figure 4. Cylindrical extrude attrition resistance as a function of crush strength.

Figure 5. Surface area as a function of sorbent bulk density.

Single Particle Kinetic Studies at LSU

Single particle kinetic tests were performed in the TGA using the E7R cylindrical extrude sorbent which was prepared using Ruthner process iron oxide. The sorbent was formulated to be similar to the E7 and E7A sorbents which were prepared earlier using pigment-grade iron oxide. The E7R sorbent contained a 1.0 ZnO:Fe₂O₃ ratio and was prepared using 5 percent bentonite and no organic binder. (The E7 and E7A sorbents were prepared using 2 percent bentonite.) Table 7 compares the reactivity and reactivity maintenance for the UCI T-2465 base-case sorbent, sorbent E7, and sorbent E7R. Sorbent E7R was the only cylindrical extrude sorbent to exhibit an increase in reactivity during the second sulfidation cycle.

Another test using base sorbent T-2465 was run to determine the effect of initial sorbent size on reactivity and reactivity maintenance. Differences were negligible.

Tables 8 and 10 summarize the single particle kinetic data (reactivity) during the first sulfidation cycle for spherical pellets and cylindrical extrudes, respectively. Tables 9 and 11 summarize the second sulfidation cycle data (reactivity maintenance) for the same sorbents. The final report of single particle kinetic studies has been submitted to AMAX R&D.

Table 7. Comparison of Sorbent
Reactivity and Reactivity Maintenance

	<u>E7R</u>	<u>T-2465</u>	<u>E7</u>
Reactivity ^a	0.291	0.229	0.182
Reactivity Maintenance ^b	1.02	0.89	0.81
ZnO:Fe ₂ O ₃ Ratio	1.0	1.0	1.0
Fe ₂ O ₃ Grade	Ruthner	Catalyst	Pigment
% Bentonite	5	2	2
% Methocel	0	0	0
Induration			
Temperature, °F	1,500	1,550	1,500
Time, Hours	4.0	4.0 2.0	4.0

a Sulfur sorption capacity (weight of S sorbed/initial sorbent weight) at time = 30 minutes.

b Ratio of 2nd cycle sulfur sorption capacity to 1st cycle sulfur sorption capacity at time = 30 minutes.

Table 8. Comparison of Pellet Reactivity

Sorbent	Reactivity*	Zn:Fe2 Ratio	Fe2O3 Grade	% Bentonite	% Starch	Induration	
						Temperature, °C	Time, Hours
P10	0.297	1.0	C	2	0	1,700	2.00
P5	0.290	0.8	P	2	0	1,900	0.25
P26	0.289	0.8	C	10	2	1,900	0.25
P11	0.285	1.0	C	2	0	1,900	0.25
P21	0.284	1.0	C	10	0	1,900	0.25
P52	0.278	0.8	C	5	2	1,900	4.00
P31	0.275	1.0	P	2	2	1,900	0.25
P12	0.257	1.0	C	2	0	1,900	4.00
P27	0.257	0.8	C	10	2	1,900	4.00
P22	0.253	1.0	C	10	0	1,900	4.00
P62	0.241	1.0	P	10	2	1,900	4.00
P47	0.222	1.0	C	5	0	1,900	4.00
1094-59	0.217	1.0	P	5	1.7	1,825	3.00
P6	0.208	0.8	P	2	0	1,900	4.00
P16	0.206	0.8	C	2	2	1,900	0.25
P32A	0.203	1.0	P	2	2	1,900	4.00
P17	0.197	0.8	C	2	2	1,900	4.00
P42A	0.194	1.0	P	5	2	1,900	4.00
P57	0.190	0.8	P	10	0	1,900	4.00
P37A	0.179	0.8	P	5	0	1,900	4.00

* Sulfur sorption capacity (weight of S sorbed/initial sorbent weight) at time = 20 minutes.

C = Catalyst-grade iron oxide.

P = Pigment-grade iron oxide.

Table 9. Comparison of Extrude Reactivity

Sorbent	Reactivity*	Zn:Fe2 Ratio	Fe2O3 Grade	% Bentonite	% Methocel	Induration	
						Temperature, OC	Time, Hours
E7R	0.291	1.0	R	5	0	1,500	4.00
T-2465	0.228	1.0	C	2	0	1,550	4.00
E13	0.211	1.0	C	2	0.5	1,700	2.00
E32A	0.211	0.8	P	2	0.5	1,500	4.00
E2	0.209	0.8	C	2	0	1,500	4.00
E1	0.207	0.8	C	2	0	1,500	0.25
E12	0.207	1.0	C	2	0.5	1,500	4.00
E11	0.200	1.0	C	2	0.5	1,500	0.25
E21	0.193	1.0	C	5	0.5	1,500	4.00
E31	0.192	0.8	P	2	0.5	1,500	0.25
E7	0.182	1.0	P	2	0	1,500	4.00
E24	0.181	1.0	C	5	0.5	1,900	0.25
E28A	0.166	0.8	P	5	0.5	1,700	2.00
E9	0.156	1.0	P	2	0	1,900	0.25
E36	0.156	1.0	P	5	0	1,500	0.25
E16	0.154	0.8	C	5	0	1,500	0.25
E38	0.153	1.0	P	5	0	1,700	2.00
E15	0.085	1.0	C	2	0.5	1,900	4.00
E35	0.054	0.8	P	2	0.5	1,900	4.00

* Sulfur sorption capacity (weight of S sorbed/initial sorbent weight) at time = 30 minutes.

R = Ruthner iron oxide.

C = Catalyst-grade iron oxide.

P = Pigment-grade iron oxide.

Table 10. Comparison of Pellet Reactivity Maintenance

Sorbent	Reactivity Maintenance*	Zn:Fe2 Ratio	Fe2O3 Grade	% Bentonite	% Starch	Induration	
						Temperature, °C	Time, Hours
1094-59	1.06	1.0	P	5	1.7	1,825	3.00
P62	0.99	1.0	P	10	2	1,900	4.00
P52	0.91	0.8	C	5	2	1,900	4.00
P6	0.90	0.8	P	2	0	1,900	4.00
P26	0.90	0.8	C	10	2	1,900	0.25
P31	0.90	1.0	P	2	2	1,900	0.25
P22	0.89	1.0	C	10	0	1,900	4.00
P27	0.88	0.8	C	10	2	1,900	4.00
P42A	0.88	1.0	P	5	2	1,900	4.00
P21	0.88	1.0	C	10	0	1,900	0.25
P10	0.84	1.0	C	2	0	1,700	2.00
P11	0.84	1.0	C	2	0	1,900	0.25
P16	0.83	0.8	C	2	2	1,900	0.25
P47	0.83	1.0	C	5	0	1,900	4.00
P12	0.82	1.0	C	2	0	1,900	4.00
P32A	0.82	1.0	P	2	2	1,900	4.00
P57	0.81	0.8	P	10	0	1,900	4.00
P5	0.79	0.8	P	2	0	1,900	0.25
P17	0.78	0.8	C	2	2	1,900	4.00
P37A	0.73	0.8	P	5	0	1,900	4.00

* Ratio of 2nd cycle sulfur sorption capacity to 1st cycle sulfur sorption capacity at time = 20 minutes.

C = Catalyst-grade iron oxide.

P = Pigment-grade iron oxide.

Table 11. Comparison of Extrude Reactivity Maintenance

Sorbent	Reactivity Maintenance*	Zn:Fe2 Ratio	Fe2O3 Grade	% Bentonite	% Methocel	Induration	
						Temperature, OC	Time, Hours
E7R	1.02	1.0	R	5	0	1,500	4.00
E12	0.92	1.0	C	2	0.5	1,500	4.00
E32A	0.91	0.8	P	2	0.5	1,500	4.00
T-2465	0.89	1.0	C	2	0	1,550	4.00
E31	0.89	0.8	P	2	0.5	1,500	0.25
E21	0.88	1.0	C	5	0.5	1,500	4.00
E11	0.85	1.0	C	2	0.5	1,500	0.25
E2	0.84	0.8	C	2	0	1,500	4.00
E1	0.83	0.8	C	2	0	1,500	0.25
E7	0.81	1.0	P	2	0	1,500	4.00
E28A	0.80	0.8	P	5	0.5	1,700	2.00
E13	0.76	1.0	C	2	0.5	1,700	2.00
E15	0.75	1.0	C	2	0.5	1,900	4.00
E16	0.75	0.8	C	5	0	1,500	0.25
E36	0.68	1.0	P	5	0	1,500	0.25
E38	0.67	1.0	P	5	0	1,700	2.00
E9	0.66	1.0	P	2	0	1,900	0.25
E35	0.63	0.8	P	2	0.5	1,900	4.00
E24	0.60	1.0	C	5	0.5	1,900	0.25

* Ratio of 2nd cycle sulfur sorption capacity to 1st cycle sulfur sorption capacity at time = 30 minutes.

R = Ruthner iron oxide.

C = Catalyst-grade iron oxide.

P = pigment-grade iron oxide.

TASK 4. BENCH-SCALE TEST ANALYSIS

Chemical analysis results were obtained on the most recently tested sorbents. Analyses of each sorbent tested in the bench-scale reactors are given in Tables 12 and 13. These tables show the zinc, iron, and sulfur contents of fresh and sulfided sorbents taken from the top, middle, and bottom portions of the fixed-bed reactors. Regenerated sorbent samples taken from the top of the reactor bed during the more recent test series after the 9th cycle have exhibited sulfur concentrations of less than 0.2 percent. Table 14 summarizes fresh and sulfided sorbent data for sorbents subjected to multi-cycle bench-scale tests.

Additional data analysis centered on the multi-cycle bench-scale reactor test series. Table 15 shows the effect of sorbent shape and iron oxide grade on sulfur sorption capacity measured at sulfur saturation. The values in the table are derived from Tables 5 and 6. In general, the cylindrical extrude shape resulted in greater sulfur sorption capacity at saturation. In addition, the catalyst-grade iron oxide formulations were found to contribute to greater sulfur sorption capacity. The differences in the results obtained from sorbents prepared using pigment- and catalyst-grade iron oxide need to be evaluated in terms of sorbent economics, however, since the pigment-grade iron oxide is significantly less expensive than catalyst grade (about \$0.75 per pound versus about \$2 per pound).

Table 12. Chemical Analysis of
Spherical Pellet Sorbents

	<u>1094-59</u>	<u>P11A</u>	<u>P6A</u>	<u>P27A</u>	<u>P37A</u>	<u>P22A</u>
<u>Zinc, %</u>						
Fresh Sorbent	23.4	26.4	23.4	20.0	22.1	23.5
Sulfided Sorbent						
Top	21.7	22.5	21.5	20.0	20.3	21.1
Middle	21.8	22.6	22.2	20.0	20.8	21.3
Bottom	21.6	22.5	21.8	19.5	20.3	22.0
<u>Iron, %</u>						
Fresh Sorbent	34.2	44.9	42.8	41.2	39.2	41.0
Sulfided Sorbent						
Top	36.3	40.6	40.1	39.9	38.5	38.2
Middle	35.4	41.3	40.0	40.0	39.2	37.3
Bottom	35.7	40.9	39.9	41.1	40.5	37.6
<u>Sulfur, %</u>						
Fresh Sorbent	--	0.06	0.02	<0.01	0.02	0.03
Sulfided Sorbent						
Top	24.0	31.5	23.5	26.8	19.9	31.8
Middle	28.1	27.1	23.9	25.8	22.4	29.4
Bottom	30.0	28.8	24.0	26.3	24.5	27.7

Table 13. Chemical Analysis of
Cylindrical Extrude Sorbents

	<u>T-2465</u>	<u>E13A</u>	<u>E7A</u>	<u>E24A</u>	<u>E28A</u>	<u>E32A</u>	<u>E2A</u>
<u>Zinc, %</u>							
Fresh Sorbent	26.9	26.8	25.8	25.1	22.4	21.8	23.5
Sulfided Sorbent							
Top	23.5	23.4	23.8	22.7	20.7	21.2	21.4
Middle	23.5	23.6	23.5	22.8	20.4	20.7	20.4
Bottom	23.5	23.5	23.5	22.4	20.5	19.5	23.5
<u>Iron, %</u>							
Fresh Sorbent	44.4	45.0	41.5	42.7	38.3	41.4	46.1
Sulfided Sorbent							
Top	40.6	40.3	39.5	39.3	37.5	39.6	42.4
Middle	40.6	40.6	39.5	39.2	36.8	39.5	42.4
Bottom	40.6	40.0	39.0	37.1	36.3	37.4	42.0
<u>Sulfur, %</u>							
Fresh Sorbent	0.04	<0.02	<0.01	0.06	0.02	0.04	0.03
Sulfided Sorbent							
Top	30.2	32.5	31.7	32.8	27.2	22.5	38.2
Middle	29.8	32.9	30.9	33.3	29.1	32.1	37.3
Bottom	30.3	32.6	31.3	34.1	29.0	33.1	37.6

Table 14. Physical Properties and Chemical Analyses of Fresh and Sulfided Sorbents

	Spherical Pellets						Cylindrical Extrudes							
	Base Case			Base Case			Base Case							
	AMAX	P11A	P6A	P27A	P37A	P22A	UCI	T-2465	E13A	E7A	E24A	E28A	E32A	E2A
1094-59	P	C	P	C	P	C	C	C	C	P	C	P	P	C
Crush Strength, lb (Pellets), lb/mm (Extrudes)	5.1	16.6	22.0	22.0	22.1	19.4	3.5	3.5	4.4	2.5	5.3	3.3	3.0	3.7
Fresh Sorbent	13.7	11.0	32.1	33.6	34.7	19.1	2.9	2.9	3.4	4.5	5.3	4.5	3.1	4.0
Sulfided Sorbent														
Attrition Resistance, %														
Fresh Sorbent	45.5	80.5	89.0	80.9	90.7	82.4	88.8	88.8	85.4	87.5	91.7	89.3	84.6	93.3
Sulfided Sorbent	69.1	68.8	97.4	83.0	96.8	79.4	78.2	78.2	82.9	90.8	89.9	93.9	93.2	88.0
Bulk Density, kg/l														
Fresh Sorbent	1.01	1.14	1.49	1.14	1.28	1.15	1.31	1.31	1.26	1.25	1.33	1.23	1.19	1.22
Sulfided Sorbent	1.12	1.28	1.59	1.25	1.51	1.27	1.46	1.46	1.42	1.40	1.49	1.36	1.33	1.37
Surface Area, m ² /g														
Fresh Sorbent	1.01	2.63	1.68	1.21	1.76	1.95	3.30	3.30	4.06	5.62	4.15	4.99	6.33	4.38
Sulfided Sorbent	3.53	1.27	2.05	1.45	2.25	1.42	1.53	1.53	2.22	5.85	2.70	6.79	4.86	2.42
Sorbent Diameter, mm														
Fresh Sorbent	4.6	4.9	4.7	4.9	4.4	4.9	5.0	5.0	4.9	4.8	4.8	4.7	4.8	4.9
Sulfided Sorbent	5.0	4.9	4.3	5.1	4.6	5.1	5.0	5.0	4.9	4.7	4.8	4.7	4.7	4.9
Fines Produced During Cyclic Testing, % <20 Mesh	0.97	1.28	0.13	0.46	0.08	0.53	0.61	0.61	0.48	0.27	0.31	0.20	0.26	0.24

P = Pigment-grade iron oxide.
C = Catalyst-grade iron oxide.

Table 15. Sulfur Sorption Capacity
as a Function of Iron Oxide Grade

	Sulfur Sorption Capacity at Saturation, lb/100 lb Sorbent		Percent of Theoretical Capacity Achieved
	<u>Theoretical</u>	<u>Observed</u>	<u>Achieved</u>
<u>Pigment-Grade Fe₂O₃</u>			
Spheres	38.1	29.5	77.4
Extrudes	38.7	35.1	90.7
<u>Catalyst-Grade Fe₂O₃</u>			
Spheres	37.0	31.0	83.8
Extrudes	38.8	37.0	95.4

Note that the theoretical sulfur sorption capacities are based on the composition of the sorbents tested and assume that the zinc and iron oxides are pure and converted to ZnS and FeS upon sulfidation.

Relationships between sorbent physical properties and sulfidation performance were sought using the data presented in Tables 5 and 6. The effect of porosity on sulfidation performance is shown in Figure 6. The bench-scale sulfidation performance was taken as the average sulfur sorption capacity (in units of pounds sulfur per 100 pounds fresh sorbent) obtained during 10 test cycles. Cumulative porosity for pores greater than 0.18 micron diameter provided the best fit. Correlation coefficients of 0.70 and 0.64 were obtained for the spherical pellets and cylindrical extrudes, respectively. Similar relationships were observed when using the reactivity values from LSU single particle kinetic studies instead of the bench-scale sulfidation data. Figure 7 shows the R20 and R30 values as a function of porosity. (R20 and R30 represent the sulfur sorption capacity of spherical pellets at an elapsed time of 20 minutes and of cylindrical extrudes at an elapsed time of 30 minutes, respectively, obtained during TGA tests.) Correlation coefficients of 0.79 and 0.64 were found for the spherical pellets and cylindrical extrudes, respectively.

The LSU R20 and R30 values correlated with AMAX bench-scale sulfidation test data, as shown in Figure 8. Correlation coefficients of 0.70 and 0.64 were obtained for the spherical pellets and cylindrical extrudes, respectively.

Figure 6. Sulfur sorption capacity at 200 ppm H_2S breakthrough as a function of porosity contained in pores $>0.18 \mu m$.

Figure 7. Single particle reactivity as a function of porosity contained in pores $>0.18 \mu m$.

Figure 8. Average sulfur sorption capacity at 200 ppm H_2S breakthrough as a function of single particle reactivity.

Total porosity values (as determined by the mercury intrusion technique using pressures up to 15,000 psi) account for pores with diameters greater than 0.012 micron. These values did not correlate well with the single particle kinetic data or with the bench-scale test data. However, porosity values for pores greater than 0.18 micron did correlate with single particle kinetic data and bench-scale test data. Apparently, the larger pores provide a pathway to the interior of the sorbent particles to allow for the sulfur gases to continue reacting. The smaller pores may become plugged fairly rapidly as the sulfidation reactions proceed (with a concurrent volume increase). Porosity values based on LSU calculations using sorbent particle and sorbent component density values do trend with the mercury intrusion porosity values, as shown in Figure 9. It would be expected that the calculated values would be generally somewhat greater than the measured values, since the measurements in this case do not detect pores smaller than 0.012 micron in diameter.

Figure 9. Calculated total porosity as a function of measured porosity (for pores $>0.012 \mu\text{m}$).

Mercury intrusion porosimetry was performed on selected sulfided sorbents. Results are shown in Table 16, along with fresh sorbent porosity for comparison. Of the four sulfided sorbents which were analyzed, the three which exhibited the best reactivity also exhibited significantly decreased pore volume upon sulfidation. The sorbent which exhibited poor reactivity (1094-59) exhibited only a slight decrease in pore volume upon sulfidation to saturation. The average pore radius of the fresh 1094-59 sorbent was also much greater than most of the other fresh sorbents. In general, the spherical pellets exhibited larger average pore radius than the cylindrical extrudes. The more reactive sorbents exhibited greater differences in porosity between fresh and sulfided forms. The 1094-59 sorbent exhibited only a slight decrease in porosity upon sulfidation.

Surface area data was analyzed to determine whether any trends with sulfidation performance could be found. Figure 10 shows the relationship between fresh sorbent surface area and the average sulfur sorption capacity at breakthrough exhibited by the sorbents. Although the correlation coefficients are low (0.68 and 0.49 for the spherical pellets and cylindrical extrudes, respectively), it appears that there is a trend of increasing reactivity with increasing surface area for the

spherical pellets. On the other hand, the average sulfur sorption capacity drops with increasing cylindrical extrude surface area. No trends between the sulfur sorption capacity at saturation and the fresh sorbent surface area were observed.

Table 16. Porosity of Fresh and Sulfided Sorbents

<u>Sorbent Identification</u>	<u>Total Pore Volume, cm³/g</u>	<u>Average Pore Radius, Angstroms</u>	<u>Porosity, %</u>	
			<u>Pores >0.180 μm</u>	<u>Pores >0.012 μm</u>
<u>T-2465</u>				
Fresh	0.256	1,550	50.1	58.2
Sulfided	0.121	1,580	28.6	32.4
<u>1094-59</u>				
Fresh	0.277	5,940	48.5	59.2
Sulfided	0.260	1,470	47.3	50.8
<u>P11A</u>				
Fresh	0.319	2,430	59.7	63.8
Sulfided	0.201	3,165	42.1	44.4
<u>P6A</u>				
Fresh	0.207	2,460	49.1	52.1
Sulfided	0.079	770	17.8	24.0

Note that porosity was determined using the mercury intrusion technique. 0.180 μ m pores are measured at an applied pressure of 1,000 psi. 0.012 μ m pores are measured at an applied pressure of 15,000 psi.

Sulfided sorbent surface areas were also examined. As shown in Figure 11, both sorbent shapes exhibited decreasing sulfur sorption capacity at breakthrough as a function of increasing sulfided sorbent surface area. Apparently, surface area decreases as sulfidation proceeds. Those sorbents which exhibited very good sulfur sorption capacity at breakthrough exhibited the lowest sulfided sorbent surface area values. No trends of saturated sorbent surface area against sorbent sulfur sorption capacity at saturation were found.

A sorbent grading system was utilized to quantify the base contract results. Table 17 shows the criteria used for the evaluations. The value ranges and grades were selected to cover the range of observed values from the test program. In cases where both sorbent shapes were subjected to the same measurements or test procedures, the value ranges for both shapes were kept the same. For example, some differences in

Figure 10. Sulfur sorption capacity at 200 ppm H₂S breakthrough as a function of fresh sorbent surface area.

Figure 11. Sulfur sorption capacity at 200 ppm H₂S breakthrough as a function of sulfided sorbent surface area.

Table 17. Zinc Ferrite Sorbent Grading System

Evaluation Category	Value Range		Grade
	Spheres	Extrudes	
<u>Chemical Reactivity Factors</u>			
1. Sulfur Sorption Capacity (1b S/100 lb Fresh Sorbent) at 200 ppm H ₂ S Breakthrough	x < 5	x < 5	1
	5 ≤ x < 10	5 ≤ x < 10	2
	10 ≤ x < 15	10 ≤ x < 15	3
	15 ≤ x < 20	15 ≤ x < 20	4
	x ≥ 20	x ≥ 20	5
2. Sulfur Sorption Capacity (1b S/100 lb Fresh Sorbent) at Saturation	x < 25	x < 25	1
	25 ≤ x < 28	25 ≤ x < 28	2
	28 ≤ x < 31	28 ≤ x < 31	3
	31 ≤ x < 35	31 ≤ x < 35	4
	x ≥ 35	x ≥ 35	5
3. Fresh Sorbent Surface Area (m ² /g)	x < 1.9	x > 4.2	3
	x ≥ 1.9	x ≤ 4.2	5
4. Fresh Sorbent Porosity (%)	x < 55	x < 35	3
	x ≥ 55	x ≥ 35	5
<u>Physical Durability Factors</u>			
1. Crush Strength (lb) Fresh and Sulfided Sorbent	x < 10	x < 3.0	1
	10 ≤ x < 15	3.0 ≤ x < 3.5	2
	15 ≤ x < 20	3.5 ≤ x < 4.0	3
	20 ≤ x < 25	4.0 ≤ x < 5.0	4
	x ≥ 25	x ≥ 5.0	5
2. Attrition Resistance (%) Fresh and Sulfided Sorbent	x < 60	x < 60	1
	60 ≤ x < 70	60 ≤ x < 70	2
	70 ≤ x < 80	70 ≤ x < 80	3
	80 ≤ x < 90	80 ≤ x < 90	4
	x ≥ 90	x ≥ 90	5
3. Fines Produced During 10 Cycles (%)	x > 0.8	x > 0.8	1
	0.6 < x ≤ 0.8	0.6 < x ≤ 0.8	2
	0.4 < x ≤ 0.6	0.4 < x ≤ 0.6	3
	0.2 < x ≤ 0.4	0.2 < x ≤ 0.4	4
	x ≤ 0.2	x ≤ 0.2	5

the value ranges were required for the determination of crush strength due to the different units reported for spherical pellets and cylindrical extrudes. Note that due to the relatively poor correlations between porosity or surface area and sulfidation performance, these factors were given a reduced weighing factor (5 percent each). In addition, only two grades were assigned rather than the 5 possible grades assigned to the other categories. These assignments are based on the information shown in Figures 6 and 10 which illustrate different responses to surface area and porosity for the two sorbent shapes.

Tables 18 and 19 show the sorbent evaluations for the spherical pellets and cylindrical extrudes, respectively. Sulfur sorption capacity at breakthrough was evaluated in terms of the averages of the first 5 and last 5 cycles. Greater weighing was placed on the average sulfur sorption capacity achieved during the last 5 cycles (15 versus 5 percent for the first 5 cycles). Sulfur sorption capacity at saturation was given a weighing factor of 20 percent, since in a commercial unit much of the sorbent bed will be subjected to full sulfidation.

The compromise between chemical reactivity and physical durability factors is evident from the values for these two different rating categories shown in the tables. In most cases, sorbents which exhibited good chemical reactivity exhibited poorer physical durability and vice versa. Table 20 summarizes the sorbent evaluation results in terms of sorbent shape and iron oxide grade. Overall improvements in physical durability were achieved for both sorbent shapes relative to the base-case sorbents. Significant improvement in reactivity was achieved for the spherical pellet sorbents relative to the base case. The reactivity ranking of one cylindrical extrude (E13A) matched that of the base case cylindrical extrude sorbent. The E13A sorbent also exhibited improvement in physical durability compared to the base case extrude. In general, the cylindrical extrude shape resulted in better overall performance. Chemical reactivity was consistently high for the cylindrical extrudes prepared using catalyst-grade iron oxide. Chemical reactivity was consistently poor for the spherical pellets prepared using pigment-grade iron oxide. Only spherical pellet sorbent P11A, which was formulated using catalyst-grade iron oxide, matched the level of reactivity observed in the catalyst-grade cylindrical extrudes. The greatest overall score was for cylindrical extrude sorbent E24A, which exhibited a good balance between reactivity and durability. The greatest overall score for spherical pellets was achieved using sorbent P11A. Several other spherical pellets approached the same value.

Table 18. Zinc Ferrite Spherical Pellet Sorbent Performance Evaluation Criteria

Sorbent Rating Category	Weighing Factor, %	1094-59		P11A		P6A		P27A		P37A		P22A	
		Grade	Points	Grade	Points	Grade	Points	Grade	Points	Grade	Points	Grade	Points
Chemical Reactivity Factors													
1. Sulfur Sorption Capacity at 200 ppm H ₂ S Breakthrough													
a. Average of First 5 Cycles	5	1	5	5	25	3	15	3	15	1	5	3	15
b. Average of Last 5 Cycles	15	1	15	5	75	2	30	2	30	1	15	3	45
Subtotal	20	--	20	--	100	--	45	--	45	--	20	--	60
2. Sulfur Sorption Capacity at Saturation	20	4	80	4	80	2	40	3	60	2	40	4	80
3. Fresh Sorbent Surface Area	5	3	15	5	25	3	15	3	15	3	15	5	25
4. Fresh Sorbent Porosity	5	3	15	5	25	3	15	3	15	3	15	5	25
Total	50	--	130	--	230	--	115	--	135	--	90	--	190
Physical Durability Factors													
1. Crush Strength													
a. Fresh Sorbent	10	1	10	3	30	4	40	4	40	4	40	3	30
b. Sulfided Sorbent	10	2	20	3	30	5	50	5	50	5	50	3	30
Subtotal	20	--	30	--	60	--	90	--	90	--	90	--	60
2. Attrition Resistance													
a. Fresh Sorbent	10	1	10	4	40	4	40	4	40	5	50	4	40
b. Sulfided Sorbent	10	2	20	2	20	5	50	4	40	5	50	3	30
Subtotal	20	--	30	--	60	--	90	--	80	--	100	--	70
3. Fines Produced During 10 Cycles	10	1	10	1	10	5	50	3	30	5	50	3	30
Total	50	--	70	--	130	--	230	--	200	--	240	--	160
Final Total	100		200		360		345		335		330		350
% of Maximum Possible Points			40		72		69		67		66		70

Note that maximum possible points = 500 (250 each for chemical reactivity and physical durability factors).

Table 19. Zinc Ferrite Cylindrical Extrude Sorbent Performance Evaluation Criteria

Sorbent Rating Category		Weighing Factor, %	UCI I-2465		E13A		E7A		E24A		E28A		E32A		E2A		
			Grade	Points	Grade	Points	Grade	Points	Grade	Points	Grade	Points	Grade	Points	Grade	Points	
<u>Chemical Reactivity Factors</u>																	
1. Sulfur Sorption Capacity																	
at 200 ppm H ₂ S Breakthrough																	
a. Average of First 5 Cycles																	
	5	5	25	4	20	4	20	4	20	3	15	2	10	2	10	3	15
	15	5	75	4	60	2	30	3	45	2	30	3	45	3	45	3	45
b. Average of Last 5 Cycles																	
	20	--	100	--	80	--	50	--	60	--	40	--	55	--	60	--	60
Subtotal																	
2. Sulfur Sorption Capacity																	
at Saturation																	
	20	4	80	5	100	5	100	5	100	5	100	4	80	5	100	5	100
3. Fresh Sorbent Surface Area																	
	5	5	25	5	25	3	15	5	25	5	25	3	15	3	15	3	15
4. Fresh Sorbent Porosity																	
	5	5	25	5	25	3	15	5	25	5	25	3	15	3	15	5	25
Total																	
	50	--	230	--	230	--	180	--	210	--	150	--	185	--	200	--	200
<u>Physical Durability Factors</u>																	
1. Crush Strength																	
a. Fresh Sorbent																	
	10	3	30	4	40	1	10	5	50	2	20	2	20	2	20	3	30
b. Sulfided Sorbent																	
	10	1	10	2	20	4	40	5	50	4	40	4	40	2	20	4	40
Subtotal																	
	20	--	40	--	60	--	50	--	100	--	60	--	40	--	70	--	70
2. Attrition Resistance																	
a. Fresh Sorbent																	
	10	4	40	4	40	4	40	5	50	4	40	4	40	4	40	5	50
b. Sulfided Sorbent																	
	10	3	30	4	40	5	50	4	40	5	50	5	50	5	50	4	40
Subtotal																	
	20	--	70	--	80	--	90	--	90	--	90	--	90	--	90	--	90
3. Fines Produced During 10 Cycles																	
	10	2	20	3	30	4	40	4	40	4	40	5	50	4	40	4	40
Total																	
	50	--	130	--	170	--	180	--	230	--	200	--	170	--	200	--	200
Final Total																	
	100		360		400		360		440		350		355		400		400
% of Maximum Possible Points																	
			72		80		72		80 88		70		71		80		80

Note that maximum possible points = 500 (250 each for chemical reactivity and physical durability factors).

Table 20. Summary of Sorbent Performance

	<u>Percentage of Maximum Possible Points</u>		
	<u>Chemical Reactivity Factors</u>	<u>Physical Durability Factors</u>	<u>Combined Physical and Chemical Factors</u>
<u>Spherical Pellets</u>			
Pigment-Grade Fe ₂ O ₃			
1094-59	52	28	40
P6A	46	92	69
P37A	36	96	66
Average	45	72	58
Catalyst-Grade Fe ₂ O ₃			
P11A	92	52	72
P27A	54	80	67
P22A	76	64	70
Average	74	65	70
Pellet Average	59	69	64
<u>Cylindrical Extrudes</u>			
Pigment-Grade Fe ₂ O ₃			
E7A	72	72	72
E28A	60	80	70
E32A	74	68	71
Average	69	73	71
Catalyst-Grade Fe ₂ O ₃			
T-2465	92	52	72
E13A	92	68	80
E24A	84	92	88
E2A	80	80	80
Average	87	73	80
Extrude Average	79	73	76

TASK 5. TOPICAL REPORT

The topical report is being assembled from previous monthly and quarterly reports and from recently obtained data analysis. A draft of the topical report will be prepared for review by METC during November.

END

**DATE
FILMED
9/01/92**