QUARTERLY TECHNICAL PROGRESS REPORT 9
OCTOBER - DECEMBER, 1988

ENHANCED DURABILITY AND REACTIVITY FOR
ZINC FERRITE DESULFURIZATION SORBENT

By
Mahesh C. Jha
Mark H. Berggren
AMAX Research & Development Center
5950 McIntyre Street
Golden, Colorado 80403-7499

Prepared for
U. S. Department of Energy
Morgantown Energy Technology Center
P. O. Box 880
3610 Collins Ferry Road
Morgantown, West Virginia 26507-0880

DOE Contract No. DE-AC21-86MC23172
AMAX Project No. 80270

March 6, 1989

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

LEGAL NOTICE

THIS REPORT WAS PREPARED BY AMAX RESEARCH & DEVELOPMENT CENTER, AS AN ACCOUNT OF WORK SPONSORED BY MORGANTOWN ENERGY TECHNOLOGY CENTER. NEITHER AMAX RESEARCH & DEVELOPMENT CENTER NOR ANY PERSON ACTING ON ITS BEHALF:

- (A) MAKES ANY WARRANTY, EXPRESSED OR IMPLIED, WITH RESPECT TO THE USE OF ANY INFORMATION, APPARATUS, METHOD, OR PROCESS DISCLOSED IN THIS REPORT OR THAT SUCH USE MAY NOT INFRINGE PRIVATELY OWNED RIGHTS; OR
- (B) ASSUMES ANY LIABILITIES WITH RESPECT TO THE USE OF, OR FOR THE DAMAGES RESULTING FROM THE USE OF, ANY INFORMATION, APPARATUS, METHOD, OR PROCESS DISCLOSED IN THIS REPORT.

TABLE OF CONTENTS

	<u>Page</u>
SUMMARY	1
INTRODUCTION	2
ACCOMPLISHMENTS	3
TASK 1. EXPERIMENTAL TEST PLAN	3
TASK 2. SORBENT PREPARATION AND CHARACTERIZATION . .	3
TASK 3. BENCH-SCALE TESTING	6
Bench-Scale Test Results	6
Single Particle Kinetic Studies at LSU	6
TASK 4. BENCH-SCALE TEST ANALYSIS	6
TASK 5. TOPICAL REPORT	6
APPENDIX A	
X-RAY DIFFRACTION ANALYSIS OF EIGHT ADDITIONAL ZINC FERRITE SORBENTS	7

LIST OF TABLES

	<u>Page</u>
Table 1. Zinc Ferrite Cylindrical Extrude Characteristics (Contract Option Formulations)	5

SUMMARY

AMAX Research & Development Center (AMAX R&D) has been investigating methods for improving the reactivity and durability of zinc ferrite desulfurization sorbents. Zinc ferrite sorbents are intended for use in desulfurization of hot coal gas in integrated gasification combined cycle (IGCC) or molten carbonate fuel cell (MCFC) applications. The reactivity of the sorbent may be defined as its sulfur sorption capacity at the breakthrough point in a bench-scale, fixed-bed reactor. The durability may be defined as the ability of the sorbent to maintain its reactivity and other important physical characteristics such as size, strength, and specific surface area during 10 cycles of sulfidation and oxidation. Two base case sorbents, spherical pellets and cylindrical extrudes used in related METC-sponsored projects, are being used to provide a basis for the comparison of physical characteristics and chemical reactivity.

During the ninth quarter of the project (October - December, 1988), a work plan for the option portion of the contract was written and forwarded to METC for approval. The contract option centers on the production of zinc ferrite sorbents using a low-cost Ruthner process iron oxide. This type of iron oxide is produced during the recovery of acid from steel plant pickle liquors. A baseline cylindrical extrude formulation containing Ruthner process iron oxide was established and prepared. Selected sorbents were forwarded to Louisiana State University (LSU) for single particle kinetic studies.

Preparation of a topical report describing the results of the base program was also begun.

INTRODUCTION

The U. S. Department of Energy (DOE), through the Morgantown Energy Technology Center (METC), has been investigating a number of advanced systems for producing electric power from large coal reserves available in the United States. The integrated gasification combined cycle (IGCC) concept has been identified as one of the most promising technologies for coal utilization. The goal of hot gas cleanup programs at METC is to develop contaminant control technologies that operate under conditions compatible with those of the gasifier and power generator (gas turbine or molten carbonate fuel cell).

Sulfur control at high temperature and pressure forms a major portion of the hot gas cleanup program at METC. Previous research has established that high temperature desulfurization can be accomplished using solid zinc ferrite sorbents to remove sulfur species from the coal gas to the 10 ppmv level or less, and the sorbent can be regenerated with air for reuse. The zinc ferrite sorbents experience chemical, physical, and thermal changes during sulfidation and regeneration. Deterioration of sorbent performance and physical characteristics is strongly influenced by the chemical composition of the sorbent and the method of preparation.

The objective of the present contract is to systematically investigate methods for enhancing the physical durability and chemical reactivity of the zinc ferrite desulfurization sorbent.

The program is divided into the following five tasks:

- Task 1. Experimental Test Plan
- Task 2. Sorbent Preparation and Characterization
- Task 3. Bench-Scale Testing
- Task 4. Bench-Scale Analysis
- Task 5. Topical Report

Accomplishments for each of the major tasks are summarized in the following section.

ACCOMPLISHMENTS

TASK 1. EXPERIMENTAL TEST PLAN

No changes were made to the experimental test plan during the reporting period.

TASK 2. SORBENT PREPARATION AND CHARACTERIZATION

The Task 2, Sorbent Preparation and Characterization, work under the base program has been completed. The sorbent preparation work under the contract option was started. The initial work centered on techniques to aid the extrusion of zinc oxide, Ruthner iron oxide, and bentonite mixtures.

Wettability tests were conducted in order to determine whether a wetting agent should be included in the zinc ferrite formulation. Complete wetting of the dry powders used for extrusion would be expected to improve flow through the extrusion chamber and die. The tests were performed using a procedure which was adapted from the Draves test for wettability of textiles. Small amounts of a dry powder mixture containing a 1:1 molar ratio of zinc oxide to iron oxide with a 2 percent bentonite addition were dropped onto the surface of solutions containing water and different concentrations of surfactant. The surfactant used was Aerosol OT (sodium sulfosuccinate). The rate at which the dry powder wets and falls through the solution surface is used to determine the effect of surfactant addition on wettability. The dry powder mixture was found to wet nearly instantly both with and without surfactant addition. As such, the addition of surfactant is not expected to improve the extrusion of the powdered oxide mixture.

Additional work centered on the optimization of the extruder feed moisture content. During the base program, extrusions were produced using 24 to 27 percent moisture in the feed. This level of moisture was too great for the Ruthner process iron oxide formulations. Limited quantities of extrudes were successfully prepared from the Ruthner process iron oxide mixture when using 18 to 22 percent moisture. The level of moisture was further optimized to allow continuous extrusion. The moisture content is important to the flow characteristics of the extrudes and to the ability to prevent buildup and packing of the mixture in the extruder.

A baseline formulation containing Ruthner process iron oxide was established and successfully prepared. The baseline formulation consisted of Ruthner process iron oxide and Asarco zinc oxide in a 1:1 molar ratio with a 2 weight percent bentonite addition. Continuous extrusion could be carried out when the moisture content of the extruder feed was maintained at 19 to 20 percent.

About 20 pounds of extrudes were prepared and dried. Five-hundred-gram batches were then indurated using different times and temperatures. Table 1 summarizes the sorbent formulations, induration conditions, and physical properties. Also shown in Table 1 are the formulations and properties of the cylindrical extrude base case sorbent prepared using catalyst-grade iron oxide (UCI T-2465) and the initial sorbent prepared using Ruthner process iron oxide (E7R, which was hand-pressed into a cylindrical shape).

A wide range of induration conditions was utilized for the Ruthner process baseline extrude formulation in order to establish the effects on strength and reactivity. Attrition resistance values of greater than 89 percent were obtained on all of the indurated sorbents. The sample which was indurated at 1,400°F for 0.25 hour was not completely converted to zinc ferrite based on the mixture of observed colors associated with both dry oxide powder mixtures and indurated sorbents.

Other activity centered on washing a sufficient quantity of Ruthner process iron oxide to make another extrude batch similar to the baseline formulation. The as-received iron oxide is being washed in a pH 11 solution of sodium hydroxide in water. Following filtration and additional washing, the filter cake will be dried and used for sorbent preparation. Analysis of chlorine in the as-received iron oxide, washed iron oxide, and selected indurated sorbents will be conducted. The preferred technique for reducing the chlorine content of the prepared sorbents will then be determined.

The dried baseline sorbent exhibited crush strength values ranging from 0 to about 0.5 pound per millimeter versus the minimum of 3.1 pounds per millimeter exhibited by the indurated sorbents. Attrition resistance was not determined on the dried sorbent.

As shown in Table 1, indurated sorbent bulk density values fell within a narrow range for the baseline Ruthner process iron oxide formulation. Bulk density values from ranging from 1.28 to 1.39 were observed. The dry sorbent bulk density was 1.41. It is speculated that the low value of bulk density recorded for the E7R sample in Table 1 may be due to the limited amount of sample available and the necessity to use a smaller container for the measurement.

Surface area was determined on selected samples prior to selection of sorbents for single particle kinetic studies at LSU. The surface areas shown in Table 1 are within the range observed previously for the UCI base case sorbent prepared using catalyst-grade iron oxide and the E7R sorbent which was prepared earlier in small quantities by hand.

Table 1. Zinc Ferrite Cylindrical Extrude Characteristics (Contract Option Formulations)

Sorbent Sample Number	Extrude Formulation				Induration Conditions		Physical Properties			BET Surface Area, $\frac{m^2}{g}$			
	Run No.	Fe ₂ O ₃ Grade	Bentonite %	Other	Temperature, of	Time, Hours	Bulk Density, kg/l	Crush Strength, lb/mm	Attrition Resistance, %				
T-2465	Base	Catalyst	2	0.5% Methocel	1,550	2.00	1.31	3.5	8.6	88.8	3.30	0.228	0.89
E7R	--	Ruthner	5	0	1,500	4.00	0.77	≈3.5	≈10	--	2.59	0.291	1.02
E41	R1	Ruthner	2	0	1,400	0.25	1.39	3.1	11.2	89.2	--	--	--
E42					1,400	0.50	1.35	3.7	10.7	90.6	3.19		
E43					1,500	0.25	1.33	3.7	11.3	91.0	--	--	--
E44					1,500	0.50	1.33	3.9	11.0	90.6	3.12		
E45					1,500	2.00	1.30	4.3	12.1	90.2	--	--	--
E46					1,500	4.00	1.28	3.9	12.5	91.0	--	--	--
E47					1,700	0.50	1.30	4.3	11.5	91.9	3.15		
E48					1,700	2.00	1.31	5.0	10.9	93.0	--	--	--
E49					1,900	0.25	1.32	5.3	10.5	94.3	2.49	--	--
E50					1,900	0.50	1.39	>7.1	9.2	95.9	--	--	--

Note: All of the formulations shown contain a 1:1 ZnO:Fe₂O₃ molar ratio. R30 is the sulfur sorption capacity of the sorbent measured during the first sulfidation cycle after 30 minutes and is expressed as grams sulfur sorbed per gram initial sorbent weight. RM30 is the ratio of the sulfur sorption capacity during sulfidation Cycle 2 to Cycle 1.

TASK 3. BENCH-SCALE TESTING

Bench-Scale Test Results

Multi-cycle bench-scale testing has been completed under the base contract. Four additional sorbents are to be subjected to multi-cycle tests under the contract option.

Single Particle Kinetic Studies at LSU

Single particle kinetic studies performed under the base contract at LSU have been completed. Additional characterizations will be performed under the option portion of the contract.

Samples E42, E44, and E47 from preparation run R1 were forwarded to LSU for single particle kinetic studies. Results are pending.

TASK 4. BENCH-SCALE TEST ANALYSIS

The mineralogical report which summarizes the characteristics of the final two sorbents tested in the bench-scale reactors under the base program is attached as Appendix A. Both sorbents (P22A spherical pellets and E2A cylindrical extrudes) were formulated using catalyst-grade iron oxide. The P22A feed sorbent contained greater than 98 percent franklinite (zinc ferrite), while the E2A sorbent contained only about 85 percent franklinite with most of the balance containing hematite. P22A was formulated using a 1:1 ZnO:Fe₂O₃ ratio. E2A was formulated using a 0.8:1.0 ZnO:Fe₂O₃ ratio. Regenerated sorbent sampled from the top of the reactor bed after the 9th oxidation step exhibited similar trends in that the E2A sorbent contained significant amounts of hematite, while P22A contained mostly franklinite. Both types of sulfided sorbent samples contained franklinite in amounts ranging from 8 to 20 percent. The major sulfided phase in both sorbent types was sphalerite. Wurtzite and pyrrhotite were also present in all of the sulfided samples.

TASK 5. TOPICAL REPORT

The topical report is being assembled from previous monthly and quarterly reports and from recently obtained data analysis. The topical report format and status were reviewed during a trip to Morgantown in December.

APPENDIX A

X-RAY DIFFRACTION ANALYSIS OF EIGHT ADDITIONAL ZINC FERRITE SORBENTS

AMAX Research & Development Center

5950 McIntyre Street • Golden, Colorado 80403-7499

(303) 273-7200

Subject: X-Ray Diffraction Analysis of
Eight Additional Zinc Ferrite
Sorbents (80270)

October 6, 1988

To: Mark Berggren

cc: T.B. Cox

From: Ron Corbett

M.C. Jha

Proj. File

Met No. 464

The sample designations covered by this report are:

GROUP OR TYPE E2A

16-10-L-RD FEED
16-10-L-RD TOP, SULFIDED
16-10-L-RD BOTTOM, SULFIDED
16-9-L-OX REGEN. SORBENT

GROUP OR TYPE P22A

17-10-R-RD FEED
17-10-R-RD TOP, SULFIDED
17-10-R-RD BOTTOM, SULFIDED
17-9-R-OX REGEN. SORBENT

The same procedures were employed as with previous runs (e.g., see my memo of 6/28/88, Met. No. 384). Semi-quantitative estimates for the compounds identified are given in tabular form on an attached page.

R.K. Corbett

RKC:jb

Attachments

X-RAY DIFFRACTION ANALYSIS
of
ZINC FERRITE SORBENTS

PHASE AND ESTIMATED WEIGHT PERCENT

Sample	Frank- linite (ZnFe ₂ O ₄)	Sphalerite (β -ZnS)	Wurtzite (α -ZnS)	Pyrrhotite (Fe _{1-x} S) + Troilite (FeS)	Hematite (Fe ₂ O ₃)	Total Unidentified
1. 16-10-L-RD, Feed	85	-	-	-	14	tr (≤ 1)
2. 16-10-L-RD, Top, Sulfided	20	44	12	24	-	tr (≤ 1)
3. 16-10-L-RD Bot., Sulfided	8	40	18	34	-	tr (≤ 1)
4. 16-9-L-OX, Regen. Sorb.	75	-	-	-	24	tr (≤ 1)
5. 17-10-R-RD, Feed	98+	-	-	-	-	tr (< 2)
6. 17-10-R-RD Top, Sulfided	10	46	14	30	-	tr (≤ 1)
7. 17-10-R-RD Bot., Sulfided	16	46	12	26	-	tr (≤ 1)
8. 17-9-R-OX, Regen. Sorb.	96	-	-	-	2	tr (< 2)

END

**DATE
FILMED
9/01/92**