DOE/ER/54134--1

DE92 016529

TECHNICAL REPORT
FIRST EIGHT MONTHS OF PROJECT
REPAIR WELDING OF FUSION REACTOR COMPONENTS

Bryan A. Chin

Submitted: May 20, 1992

Materials Engineering
Department of Mechanical Engineering
Auburn University
Auburn, AL 36849
Phone: 205-844-3322

Document WP51WP14FUSION21

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

MASTER

ep

TABLE OF CONTENTS
CONTINUATION APPLICATION

I. Abstract of Proposed Research	1
II. Statement of the Problem.	2
III. Review of Prior Investigations.	3
IV. Project Objectives	5
V. Project Results to Date	6
A. Preparation of Materials	6
B. Task A: Modeling	7
C. Task B: Stress State Effects	7
D. Publications and Conferences	8
VI. References	9

I. ABSTRACT OF ONGOING RESEARCH

Recent experimental investigations indicate that the repair welding of irradiated materials containing greater than 1 to 2.5 appm helium leads to catastrophic cracking in the heat affected zone of the weld. The high temperatures and cooling tensile stresses which occur during the welding process lead to enhanced helium bubble growth in the heat affected zone region, resulting in catastrophic cracking upon cooling. An investigation is proposed which seeks to determine the effect of stress state on the helium bubble growth process and develop engineering modifications to the welding process based upon this understanding in an attempt to alleviate or eliminate the weld cracking problem in type 316 stainless steel materials.

II. STATEMENT OF PROBLEM

The first wall of a fusion reactor will be subjected to intense neutron irradiation and cyclic stress resulting from thermal fluctuations experienced during plasma ignition. In addition the first wall must withstand abnormal events such as those produced by a plasma disruption. These events produce irreversible degradation in the properties of the first wall material and play a decisive role in limiting the useful life of fusion reactor components. Repair and replacement of components will be required. Current commercial designs envision replacing segments of the first wall at periodic maintenance intervals. Such replacement and repair would be greatly enhanced if welding were possible.

Unfortunately recent experimental data suggests that welding of irradiated material will at best be difficult. Recent attempts to repair cracks in irradiated reactor vessels at the Savannah River Project have not been successful [1-3]. Patches were welded over reactor tank material containing 3 appm helium in an attempt to repair stress corrosion cracks. Subsequent examination revealed extensive cracking in the heat affected zone of the patch welds.

Additionally welds were made on fusion heat Type 316 SS with helium contents between 1 and 250 appm [4,5]. These bead on plate welds cracked upon cooling (see Figure 1). Analyses revealed that cooling stresses lead to the nucleation and growth of grain boundary helium bubbles which resulted in catastrophic cracking in the heat affected zone (HAZ) and molten metal fusion zone. Catastrophic cracking was found to occur in all materials containing greater than 2.5 appm helium. During normal operation of commercial fusion reactors, helium concentrations are anticipated to exceed 1000 appm in first wall materials.

III. REVIEW OF PRIOR INVESTIGATIONS

Welding processes produce internal stresses and elevated temperatures which accelerate the growth of helium bubbles, leading to the catastrophic cracking as seen in Figure 1. Previous attempts to join irradiated materials containing helium via gas tungsten arc welding have been made by several investigators, the results being mixed [1-10]. Hall et al [6] welded thin wall AISI 304 stainless steel tubing which was irradiated in Experimental Breeder Reactor-II (EBR-II) at temperatures between 454°C and 487°C to fast fluences ranging from 1.38×10^{26} to 7.51×10^{26} n/m² ($E > 0.1$ Mev). The welds were made using only a small constraint to hold the parts together while welding in the hot cell. Intergranular cracking was observed in the HAZs of a small fraction of these specimens. The He concentration of these materials was not measured but is estimated to be between 3 to 15 appm.

Atkin [7] performed gas tungsten arc (GTA) welding of 20% cold worked (CW) 316 stainless steel that had been irradiated in EBR-II at 400°C to a peak fluence of 1.26×10^{27} n/m² ($E > 0.1$ Mev). The welds were made on material taken from reactor coolant ducts and were welded in an unconstrained condition. Based upon known irradiation conditions and measurements on materials seeing similar irradiation conditions, we estimate the helium content of the material to be between 4 and 25 appm. After welding the specimens were bend tested. Visual examination indicated the welds to be sound and free from cracks. However no detailed examinations or further analyses were conducted.

Watanabe [8] has also reported welding of 10% CW 316 stainless steel that was taken from wrapper tubes irradiated in JOYO at 400°C to a maximum helium content of 9 appm. GTA welds with filler metal additions were made on strips similar in configuration to the specimens prepared by Atkin. The section which

was being welded was allowed to float free during the welding process. Welded specimens appeared to be sound. Tensile specimens taken from the weld region failed in the heat affected zone and showed a loss in ductility. The authors observed intergranular cracking in the heat-affected zone which was attributed to helium bubble formation during welding.

Recently an effort was initiated to repair stress-corrosion cracks in an irradiated stainless steel reactor vessel at the Savannah River Site [1-3]. Patches were gas tungsten arc welded over the stress-corrosion cracks in a vessel which was measured to contain 3 appm of helium. Previous repairs of a similar vessel earlier in life had been successfully performed [4], the major difference being the increase in helium content due to further irradiation exposure. Examinations after the welding was complete revealed extensive cracking in the HAZ of the patch welds. Analyses by the Savannah River Project Personnel indicate the cracking is associated with helium bubble growth at the grain boundaries in the heat affected zone.

For the last two years a joint project has been conducted between Auburn University, Sandia National Lab (SNL) and Oak Ridge National Lab (ORNL) to determine the feasibility of welding helium containing materials [4,5]. To avoid the difficulties associated with hot cell operations and reduce radiological hazards, initial investigations were carried out on helium charged 316 stainless steel. In this process, the material is charged with tritium at elevated temperatures and pressures. The tritium is then allowed to decay to helium and the excess tritium is pumped off. In this manner materials containing between 1 and 250 appm helium were produced. Homologous bead-on-sheet gas tungsten arc welding of this material was conducted. In all sheet material containing greater than 2.5 appm helium catastrophic cracking occurred after the weld was completed.

These cracks were found to be the result of helium bubble growth along grain boundaries during cooling of the welds. A theoretical model which describes the growth of helium bubbles along the grain boundaries was developed [4]. The model indicates that the helium bubble growth is very sensitive to thermally induced cooling stresses. A preliminary experiment was conducted that modified the stress state during cooling. No cracking was found in the welds produced in this manner.

In summary, based upon all reported experiments conducted to date there are two parameters which control the catastrophic cracking observed in the welding of irradiated materials. These parameters are helium content and the constraint used during welding of the specimens. From experiment, there appears to be a threshold level of helium content which must be exceeded before cracking occurs. This threshold limit is between 1 and 2.5 appm helium for 316 SS. The second parameter which appears to control the cracking is the constraint used during welding. This constraint plays a major role in determining the stress state that results during cooling of the weld. Both the high temperature surrounding the molten metal pool of the welding process and the tensile stress state experienced by the HAZ during cooling lead to the nucleation and growth of grain boundary helium bubbles. Catastrophic cracking occurs along these grain boundaries with a high level of helium bubble concentration leading to failure of the weld specimen.

IV. PROJECT OBJECTIVES

To insure that a technology is available which can be used to adequately repair fusion reactor components, the following scientific study is proposed. The objectives are:

1. to investigate the effect of stress state during cooling on the weld

cracking in Type 316 SS.

2. to identify alterations in the welding process that will alleviate or eliminate the weld cracking observed in irradiated materials.

V. PROJECT RESULTS TO DATE

A. PREPARATION OF MATERIALS

To expedite and reduce the costs and hazards associated with the welding of irradiated materials an investigation which utilizes unirradiated, helium doped, previously irradiated FFTF and HFIR discarded specimens and newly irradiated HFIR material is underway. Efforts during the initial stages of the contract have concentrated on helium doping of additional materials for testing and identification of previously irradiated materials for hot cell welding experiments. In October 1991 one week after award of this grant, specimens were manufactured for Helium doping at SRL. A new pressure vessel for tritium charging was procured and qualified for pressurized tritium work as required by SRL. Specimens were load in January 1992 and the charging procedure initiated to obtain doses of 0.5, 1.0, 5.0 and 10.0 appm. Specimens containing 0.5 was received at ORNL in May 1992. Samples from these specimens have been sent for helium analysis by Rockwell International.

Doping to 1 appm levels has been completed. However specimens have not been received at ORNL. Some difficulty with establishing safety procedures to handle tritium containing materials has been encountered which is limiting progress in initiating planned experiments. Helium doping to 5 and 10 appm levels are underway.

Irradiated HT-9 material for weld studies have been found in the HEDL stock

of obsolete specimens and will be sent to ORNL for hot cell testing in the next shipment of irradiated materials.

B. TASK A: MODELING

A simple model of the nucleation and growth process of helium bubbles along grain boundaries during welding has been developed by the authors [4] to describe the observed weld cracking in stainless steel materials. This simplistic model applies theories describing nucleation and growth of gas filled pores in solids [11-14] to the specific conditions encountered during the welding process. As the weld torch passes a given position on the plates being welded the stress state at that position changes. For a fully constrained weld, the state of stress is hypothesized to progress from an initial state of no stress to compressive stress to zero stress to a tensile stress. Only during the last state of stress (tensile stress) is significant helium bubble growth predicted. The model has been altered to analyze the effect of different compressive stress on the helium bubble growth. Time measurements from video tapes of the welding of helium doped materials and measurements of final helium bubble size required to cause fracture have been compared with predictions of the model. Good agreement between fracture surface bubble size measurements and predictions were obtained. Additionally the model and experimental results appear to be in agreement with respect to time at which cracking initiates.

C. TASK B: STRESS STATE EFFECTS

This task is investigating the effect of a change in stress state on the grain boundary helium bubble growth and weld cracking through separate experiments. Preliminary experiments have been completed in which a compressive

stress was applied to the plate edges while welding the tritiated material. Visual examination indicated no visible cracking of tritium containing welds. However detailed SEM examinations indicated helium bubble growth along grain boundaries perpendicular to the applied stress.

D. PUBLICATIONS AND CONFERENCES

The Auburn Fusion Materials Group completed the following publications and presentations during the first year of the grant.

T.J. Miller, S.J. Zinkle and B.A. Chin, "Strength and Fatigue of Dispersion-Strengthened Copper," Journal of Nuclear Materials, V179, (1991), pp. 263-269.

G.R. Rao, B.A. Chin and A. Rowcliffe, "Development of Miniature Fatigue Specimens for Structural Materials Testing," Journal of Nuclear Materials, V179, (1991), pp. 438-513.

H.T. Lin and B.A. Chin, "Feasibility of Welding Irradiated Materials," Journal of Nuclear Materials, V179 (1991), pp. 1131-1135.

H.T. Lin and B.A. Chin, "Helium Induced Weld Cracking in Austenitic and Martensitic Steels," Journal of Materials Science, 26, 1991, pp. 1-9.

C.K. Lee, B.A. Chin, S. Zinkle and R.C. Wilcox, "Brazing of Copper-Alumina Alloys," accepted for publication in Journal of Nuclear Materials, January, 1992.

C.A. Wang, H.T. Lin, M.L. Grossbeck and B.A. Chin, "Suppression of HAZ Cracking During Welding of Helium-Containing Materials," accepted for publication in Journal of Nuclear Materials, January, 1992.

C.A. Wang, R.L. Klueh and B.A. Chin, "The Weldability of Low Activation Cr-W Steels," accepted for publication in Journal of Nuclear Materials, October, 1991.

VII. REFERENCES

1. W. R. Kanne, C. L. Angerman and B. J. Eberhard, "Weldability of Tritium-Charged 304L Stainless Steel," DP-1740, E. I. DuPont Co., Savannah River Laboratory, Aiken, SC, (Feb. 1987).
2. W.R. Kanne, "Helium Embrittlement Cracking During Patch Welding in Savannah River C Reactor," DPMS-8940, E.I. Dupont Co., Savannah River Laboratory, Aiken, SC, (1989).
3. A.K. Birchenall, "Helium Induced Weld Cracking in Irradiated 304 Stainless Steel," DPMS-8941, E.I. Dupont Co., Savannah River Laboratory, Aiken, SC (1989).
4. H.T. Lin, M.L. Grossbeck and B.A. Chin, "Cavity Microstructure and Kinetics During Gas Tungsten Arc Welding of Helium-Containing Stainless Steel," Metallurgical Transactions A, V21A, September 1990, pp. 2585-2596.
5. H.T. Lin, S.H. Goods, M.L. Grossbeck and B.A. Chin, "Helium Induced Degradation in the Weldability of an Austenitic Stainless Steel," ASTM-STP 1046, 1990, pp. 301-314.
6. M.M. Hall, Jr., A.G. Hins, J.R. Summers and D.E. Walker, "Weldments: Physical Metallurgy and Failure Phenomena," in proceedings of 5th Bolton

- Landing Conference, August, 1978, General Electric Co., Schenectady, NY, 1979, pp. 365-378.
7. S.D. Atkin, ADIP Semiannual Progress Report, September 30, 1981, DOE/ER-0045/7, U.S. Dept. of Energy, Office of Fusion Energy, pp. 110-117.
 8. K. Watanabe, A. Hishinuma and T. Kodaira, "Weldability of Neutron-Irradiated Type 316 Stainless Steel," to be published in Journal of Nuclear Materials, Proceedings of the Fourth Conference on Fusion Reactor Materials, December 4-8, 1989, Kyoto, Japan, Paper number 7-097.
 9. J. P. Maloney, et al., "Repair of a Nuclear Reactor Vessel," DP-1199, E. I. DuPont Co., Savannah River Laboratory, Aiken, SC, (June 1969).
 10. H.T. Lin and B.A. Chin, "The Feasibility of Welding Irradiated Materials," to be published in Journal of Nuclear Materials, Proceedings of the Fourth International Conference on Fusion Reactor Materials, December 4-8, 1989, Kyoto, Japan, Paper number 7-098.
 11. A. J. Markworth, "On the Coarsening of Gas-Filled Pores in Solids," Metallurgical Transactions, 4A, 1973, pp. 2651-2656.
 12. D. Hull and D. Rimmer, "The Growth of Grain-Boundary Voids Under Stress," Phil. Mag., 4, 1959, pp. 673-687.
 13. E. D. Hyam and G. Sumner, "Irradiation Damage to Beryllium," Proc. Conf. Radiation Damage in Solids, Vol. 1, IAEA, Vienna, 1962, pp. 323-331.
 14. W. Beere, "The Growth of Sub-Critical Bubbles on Grain Boundaries," J. Nucl. Mater., 120 (1984), pp. 88-93.

END

**DATE
FILMED**

8 / 11 / 92