DOE/PC/80011-T6

APC1

DEVELOPMENT AND PROCESS EVALUATION OF
IMPROVED FISCHER-TROPSCH SLURRY CATALYSTS

DOE/PC/80011--T6

DE92 016985

6th

QUARTERLY TECHNICAL PROGRESS REPORT
FOR THE PERIOD 1 JANUARY TO 31 MARCH 1988

by

Howard P. Withers

Air Products and Chemicals, Inc.

Allentown, PA 18195

JUL 00 1988

and

Dragomir B. Bukur and Michael P. Rosynek

Departments of Chemical Engineering and Chemistry

Texas A&M University

College Station, TX 77843

WORK PERFORMED UNDER DOE CONTRACT NO. DE-AC22-85PC80011

FOR THE UNITED STATES DEPARTMENT OF ENERGY

THE PITTSBURGH ENERGY TECHNOLOGY CENTER

PITTSBURGH, PENNSYLVANIA

MASTER

7/18

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

DISCLAIMER

This report was prepared as an account of work sponsored by the United States Government. Neither the United States nor the United States Department of Energy, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, mark, manufacturer, or otherwise, does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

Project Manager - George Cinquegrane
Liquid Fuels Division
Pittsburgh Energy Technology Center
Pittsburgh, Pennsylvania

Program Manager - John Shen
Office of Coal Preparation & Liquefaction
Department of Energy
Washington, DC

2738t

TABLE OF CONTENTS

I. Abstract	1
II. Objective and Scope of Work	3
III. Summary of Progress	4
IV. Detailed Description of Technical Progress	9
Task 1 - Project Work Plan	9
Task 2 - Slurry Catalyst Improvement	9
2.1. Development of Wax Analysis Procedure	9
2.2. Slurry Reactor Wax Withdrawal Studies	13
2.3. TASK 2.2 - Binder Support Effect Research	14
2.3.1. Tests of SiO ₂ -Containing Catalysts	14
2.3.2. Run FA-73-0828 (100 Fe/5 Cu/4.2 K/8 Al ₂ O ₃)	18
2.4. TASK 2.4 - Activation/Reduction Procedure Research	20
2.4.1. Run FB-25-0098 (100 Fe/3 Cu/0.2 K)	20
2.5. TASK 2.5 - Slurry Reactor Kinetic Studies	20
2.5.1. Run SB-07-0458 (100 Fe/0.3 Cu/0.5 K)	20
2.5.2. Run SA-07-0468 (100 Fe/0.3 Cu/0.5 K)	22
2.5.3. Run SA-25-2657 (100 Fe/3 Cu/0.2 K)	24
2.5.4. Kinetic Parameter Estimation - Background	25
2.5.5. Kinetic Parameter Estimation - Run SA-05-3657	27
2.6. Additional Fixed Bed Catalyst Tests	29
2.6.1. Run FA-01-0128 (United Catalyst' C-73 Fused Iron)	29
2.6.2. Run FA-15-0278 (100 Fe/1 Cu/0.2 K)	30
2.7. Catalyst Preparation and Characterization	31
2.7.1. Synthesis and Elemental Analysis of Alumina-Supported Precipitated Iron Catalysts	31
2.7.2. Reduction Studies of Supported, Precipitated Catalysts	32
2.7.3. Characterization of Silica Gel-Supported Impregnated Catalysts	34
Task 3 - Process Evaluation Research	36
V. Literature References	38
Tables	39
Figures	78
Appendix I. Summary of Catalyst Synthesis and Drying Procedure	122

I. ABSTRACT

During the past quarter, we have completed 7 runs in fixed bed reactors and 3 runs in slurry reactors. A slurry reactor run using Ruhrchemie LP 33/81 catalyst was begun, and this run is still in progress. Three SiO_2 -containing catalysts with nominal compositions of 100 Fe/5 Cu/4.2 K and 8, 25, and 100 parts SiO_2 have been tested. The activity of the catalyst containing 8 parts SiO_2 was high, the most active of all catalysts tested thus far. This catalyst also produced low amounts of methane and C_2 - C_4 products relative to catalysts tested previously. As the silica content of the catalyst increased, catalyst activity decreased and the catalysts produced more methane and C_2 - C_4 products. A 100 Fe/5 Cu/4.2 K/8 Al_2O_3 catalyst has also been tested in fixed bed. The alumina-containing catalyst had high activity, but was not as active as the catalyst containing the same nominal amount of silica and made greater amounts of lower molecular weight products. We have also repeated three previous catalyst tests: reduction/activation using CO at 250 °C, 24 h, a catalyst test of precipitated 100 Fe/1 Cu/0.2 K, and a test of 170/230 mesh United Catalyst' C-73 fused iron.

A slurry run using 100 Fe/3 Cu/0.2 K catalyst was completed, and the initial activity of the catalyst was high; however, the catalyst rapidly deactivated after the first mass balance and withdrawal of accumulated reactor wax. After this run was completed, different methods of wax withdrawal were tested and we adopted a procedure of removing accumulated slurry to an external settling tank for gravity settling of catalyst and wax. This modification was installed on both slurry reactors for future slurry runs. Two runs using 100 Fe/0.3 Cu/0.5 K catalyst were made to study the effect of slurry reduction procedure (H_2 and CO reductants, 280 °C, 0.79 MPa). The catalyst reduced with H_2 for 24 h became more active with time, which was also observed in a fixed bed reactor. The catalyst reduced using CO for 16 h had a comparable activity to a fixed bed test of a similar catalyst composition, but the catalyst activity declined quickly. The decline in activity may have been due in part to operational difficulties during the initial periods of the run.

Kinetic parameters have been estimated for a 100 Fe/0.3 Cu/0.2 K catalyst from data taken in a previous slurry reactor run. A Langmuir-Hinshelwood model, derived from the carbide mechanism with inhibition by water, was found to fit the data for the Fischer-Tropsch reaction rate. The

apparent activation energy for this reaction was found to be 94.6 kJ/mol . The water-gas shift reaction rate was fit to a mass action rate expression, using the same denominator as the Fischer-Tropsch expression, and this rate was also correlated by a simple first order in CO rate expression.

Precipitated, promoted iron catalysts having the composition 100 Fe/5 Cu/5 K₂O and containing varying amounts of silica (SiO₂) and alumina (Al₂O₃) binder/support have been synthesized. X-ray photoelectron (XPS) and Fourier Transform infrared (FT-IR) spectroscopies, coupled with isothermal and temperature-programmed reduction (TPR) measurements, have been used to characterize the reduction properties and resulting chemical state and behavior of surface sites on these materials. These studies have been extended to include additional silica gel supported catalysts prepared by an impregnation technique and containing 25 weight % Fe. The presence of 8 parts by weight of either SiO₂ or Al₂O₃ per 100 parts of Fe has relatively little effect on the reduction surface properties of the precipitated catalysts. Larger amounts (20 to 100 parts by weight) of either binder/support, however, significantly retard the rate and extent of iron reduction at 300 °C in both H₂ and CO. XPS measurements indicate that, following either reduction in H₂ at 300 °C or exposure to 1 atm of a 2/1 mixture of (H₂/CO) at 250°C, potassium promoter forms a thin, highly dispersed layer on the surfaces of both the 100 Fe/5 Cu/5 K₂O/8 SiO₂ and 100 Fe/5 Cu/5 K₂O/8 Al₂O₃ catalysts, but does not redisperse on the material containing 25 parts of SiO₂ support. It is likely that surface water plays an important role in promoting the potassium redispersion process.

A new Varian 3400 gas chromatograph has been received and installed, and a wax analysis procedure using this instrument has been developed. A 0.53-mm ID x 15-m RSL-150 (polydimethylsiloxane) column is used to perform the separation. The analysis can give results for compounds up to C₄₅-C₅₀. An internal standard (*n*-hexadecane) is used to calculate absolute weight fractions, and indicates that typically greater than 60 % of the sample is eluted from the column and detected. The wax analysis will enable us to extend our detailed analyses up to higher carbon numbers than were previously possible.

II. OBJECTIVE AND SCOPE OF WORK

The objective of this contract is to develop a consistent technical data base on the use of iron-based catalysts in Fischer-Tropsch (F-T) synthesis reactions. This data base will be developed to allow the unambiguous comparison of the performance of these catalysts with each other and with state-of-the-art iron catalyst compositions. Particular attention will be devoted to generating reproducible kinetic and selectivity data and to developing reproducible improved catalyst compositions. To accomplish these objectives, the following specific tasks will be undertaken.

TASK 1 - Project Work Plan

The objective of this task is to establish a detailed project work plan covering the entire period of performance of the contract. This includes estimated costs and manhours expended by month for each task.

TASK 2 - Slurry Catalyst Improvement

The primary purpose of this task is to develop improved iron-based catalysts, both precipitated and supported, that show enhanced activity and selectivity in slurry phase testing. This will be accomplished by gaining systematic understanding of the role of promoters, binders, supports and activation procedures in determining the activity and selectivity of iron-based catalysts. The catalyst development program will incorporate extensive physical and chemical characterization of these materials with the objective to establish correlations between the physical/chemical properties of these catalysts and the corresponding catalytic behavior for synthesis gas conversion.

TASK 3 - Process Evaluation Research

The purpose of this task is to subject the most improved catalysts (based on activity and selectivity) to a thorough process evaluation. This involves long term stability studies, investigation of a wide range of process variables, and determination of kinetic parameters.

TASK 4 - Economic Evaluation

The aim of this task is to develop the relative economic impact for each improved catalyst composition and compare these economics with the economics of using the base case catalyst.

III. SUMMARY OF PROGRESS

- Fixed Bed Reactor Tests.

Three SiO_2 -containing catalysts have been tested. The catalysts had nominal compositions of 100 Fe/5 Cu/4.2 K and 8 (run FA-63-0418), 25 (FA-66-0548), and 100 parts SiO_2 (FA-69-0668). The activity of the 100 Fe/5 Cu/4.2 K/8 SiO_2 -containing catalyst was particularly high, giving an (H_2 -CO) conversion of 65.1 % at 250 °C, 1.48 MPa, 4 Nl/g-cat·h, (H_2/CO) = 1. The 8 parts SiO_2 catalyst also favored the formation of high molecular weight products (C_5+). As the SiO_2 content increased to 25 and 100 parts per 100 parts Fe, catalyst activity decreased, in part due to the lower concentration of active metal (Fe) in the catalyst. The methane and C_2 - C_4 fractions of the hydrocarbon product also increased as the SiO_2 concentration increased. The catalysts with 8 and 25 parts SiO_2 deactivated at high pressure (2.96 MPa), but higher concentrations of SiO_2 appeared to inhibit the deactivation.

An Al_2O_3 -containing catalyst (nominal 100 Fe/5 Cu/4.2 K/8 Al_2O_3 , run FA-73-0828) has also been tested in a fixed bed reactor. The initial activity of the catalyst was low, but increased with time on stream. The ultimate activity of the catalyst was high, but less than the activity of the catalyst containing 8 parts SiO_2 . The presence of alumina also appeared to favor the formation of methane and C_2 - C_3 products, as these fractions were higher than with catalysts containing silica.

Three retests of previous fixed bed runs have been made to improve our results of selected tests. A reduction/activation run using 100 Fe/3 Cu/0.2 K catalyst reduced with CO for 24 h at 250 °C was made (run FB-25-0098). In the previous test, the catalyst activity declined more rapidly than expected from the results using 8 h reduction durations; however, this result was confirmed in this retest. The activity and selectivity trends of both runs were similar in all respects. A retest was also made of the 100 Fe/1 Cu/0.2 K catalyst (run FA-15-0278) which had been tested previously using a slightly different reduction procedure. The activity and selectivity during the first balance were similar to that of the previous run, but the catalyst deactivated rapidly during subsequent balances. A run was made using 170/230 mesh United Catalyst' C-73 fused iron (run FA-01-0128). Since the original tests of this catalyst, several improvements in reactor temperature control have been made on the fixed bed systems, and a retest was made to improve our results on particle size effects

with this catalyst. The initial activity of the catalyst was lower than expected, but after the first mass balance the activity improved and the ($H_2 + CO$) conversions were comparable to or greater than that obtained in previous tests.

- Slurry Reactor Runs.

A run was made using 100 Fe/3 Cu/0.2 K catalyst (run SA-25-3657) reducing the catalyst under optimum conditions (CO at $280^\circ C$ for 24 h). During the first balance, the activity of the catalyst was high, greater than that in the fixed bed test of the same catalyst: 83.0 (slurry) versus 72.2 % (fixed bed) at $250^\circ C$, 1.48 MPa, $H_2/CO = 1$. Following the first balance, a wax withdrawal was made, and in the next balance the catalyst began to deactivate rapidly. After the run was terminated at 430 h on stream, we attempted to improve the wax withdrawal technique to minimize the disturbance to the catalyst during withdrawals. Two methods using filters were tested, but neither worked under realistic conditions using finely ground catalyst in paraffin wax. Withdrawing excess slurry to an external settling tank was successful. Once removed from the reactor, the excess slurry was allowed to separate into wax and concentrated slurry layers. The wax, containing only small amounts of catalyst, was removed and quantified and the concentrated slurry was returned to the reactor. The external settling tank system was installed on both slurry reactors and was used to remove accumulated products during subsequent runs.

Two slurry reactor tests of 100 Fe/0.3 Cu/0.5 K catalyst, each using a different reduction procedure, have been made. The reduction conditions were H_2 reductant for 24 h (run SB-07-0458) and CO reductant for 16 h (run SA-07-0468), both at $280^\circ C$ and 0.79 MPa. The activity of the H_2 reduced catalyst increased with time on stream, which also occurred during the fixed bed tests using H_2 reductant. From 45 to 428 h on stream, the ($H_2 + CO$) conversion increased from 24.8 to 35.5 % (at $250^\circ C$, 1.48 MPa, $H_2/CO = 1$). Balances at lower feed ratio (0.68 nominal) appeared to facilitate the activation of the catalyst. The CO reduced catalyst had high activity during the start of the run, comparable to the fixed bed results using catalyst of similar composition, however, the catalyst deactivated after the second mass balance was made. Several process interruptions occurred during the early balances, and it is not clear what caused the catalyst deactivation.

A stability test of the Ruhrchemie LP 33/81 catalyst (run SA-99-0888) has been initiated.

The catalyst was reduced using CO at 280 °C for 16 h, and following reduction the catalyst was tested at a fixed set of operating conditions (250 °C, 1.48 MPa, 2 NL/g-cat·h, H₂/CO = 0.67). The catalyst appeared to be stable, giving an average (H₂+CO) conversion of about 45 % after stabilizing at approximately 18 h on stream. This run is still in progress.

The data of run SA-05-2957 were used to obtain estimates of kinetic parameters for the Fischer-Tropsch and water-gas shift reactions. A disappearance model for the Fischer-Tropsch reaction, derived from the carbide mechanism with inhibition by water, was found to give the best fit to the data from this run. The estimated activation energy was 94.6 kJ/mol, in good agreement with other studies of Fischer-Tropsch kinetics. Two expressions were used to correlate water-gas shift activity: mass actions kinetics, using a shared denominator with Fischer-Tropsch, and a first-order in CO rate. Both rate forms fit our data reasonably well.

• Catalyst Preparation and Characterization.

Using a modification of the catalyst preparation procedure described previously, three alumina-containing precipitated iron catalysts have been prepared, having the nominal compositions 100 Fe/5 Cu/4.2 K/*x* Al₂O₃, where *x* = 8, 25, and 100. Elemental analyses of the synthesized catalysts by atomic absorption spectroscopy revealed that the maximum Al₂O₃ content obtainable by the alkoxide impregnation/hydrolysis technique employed to prepare these materials is less than 35 parts by weight per 100 parts of Fe. Elemental analyses have been completed for each of the six silica- and alumina-supported catalysts; analyzed contents of Fe, Cu, and K were close to the expected nominal values in each case.

Isothermal and temperature-programmed (TPR) reduction studies of the supported catalysts have demonstrated that reduction behaviors at 300 °C of the materials containing 8 parts of either SiO₂ or Al₂O₃ binder closely resemble those of the previously reported unsupported 100 Fe/3 Cu, 0.2 K composition for both H₂ and CO reductants. Following initial rapid reduction of CuO promoter to metallic Cu, facile reduction of Fe₂O₃ to Fe₃O₄ occurs, giving rise to a TPR peak at ~300 °C. A second broad peak, corresponding to conversion of Fe₃O₄ to metallic Fe occurs at 700-800 °C. However, isothermal reduction profiles obtained at a constant temperature of 300 °C, which more closely simulates typical catalyst pretreatment conditions, illustrate that, although the

initial $\text{Fe}_2\text{O}_3 \rightarrow \text{Fe}_3\text{O}_4$ reduction step occurs readily for all three SiO_2 -containing catalysts, the rate of subsequent reduction of Fe_3O_4 to metallic iron decreases markedly with increasing level of SiO_2 support. X-ray photoelectron spectroscopy and TPR studies of SiO_2 -supported materials demonstrate that, although extensive formation of reduced, metallic iron occurs for the two catalysts containing 8 parts of binder, for catalysts containing 25 and 100 parts SiO_2 , pretreatment for 16 h at 300 °C in either H_2 or CO results in very little formation of either surface or bulk zero-valent iron.

Additional X-ray photoelectron spectroscopy (XPS) measurements indicate that, following either reduction in H_2 at 300 °C or exposure to 1 atm of a 2/1 mixture of H_2/CO at 250 °C, potassium promoter forms a thin, highly dispersed layer on the surfaces of both the 100 Fe/5 Cu 4.2 K/8 SiO_2 and 100 Fe/5 Cu/4.2 K/8 Al_2O_3 catalysts, but does not redisperse on the material containing 25 parts of SiO_2 support. It is likely that surface water plays an important role in promoting the potassium redispersion process. This conclusion is supported by the marked (100-fold) increase in intensity of the K 2p XPS peaks that occurs following exposure of the catalysts to conditions that generate water (reduction in H_2 or H_2/CO reaction). Reduction in CO at 300 °C, by contrast, does not effect an increase in K 2p peak intensity, but subsequent exposure of the reduced catalyst to a H_2/CO mixture at 250 °C results in the same redispersion of potassium promoter as that observed for the H_2 -reduced catalyst prior to H_2/CO exposure.

- Wax Analysis Procedure.

We have completed our work on an analytical procedure for product wax using a new Varian 3400 gas chromatograph. Four different capillary columns were evaluated to perform the separation, and an RSL-150 (polydimethylsiloxane) wide-bore capillary (0.53-mm ID $\times$ 15-m) was selected for our samples. Solubility tests of a variety of solvents using hard paraffin wax (FT-300) and fixed bed product wax indicated that the most suitable solvent for wax is CS_2 , and with a representative fixed bed wax sample the column conditions and sample size/dilution were varied to optimize the analysis. An internal standard method (*n*-hexadecane) was used to estimate the sample recovery, and it was found that greater than 60 % of the sample injected is eluted from the column and detected. Compounds with carbon numbers of C_{45} - C_{50} can be analyzed. The effect of the wax

analysis on lumped hydrocarbon distributions (with unanalyzed wax) is small for the methane, C_2-C_4 , and C_5-C_{11} fractions. Minor changes in the numerical values of these fractions occur due to small amounts of oxygenates and C_9-C_{11} hydrocarbons present in the wax sample.

IV. DETAILED DESCRIPTION OF TECHNICAL PROGRESS

TASK 1 — Project Work Plan

The project work plan was completed during the first quarter of this project and the detailed work plan was submitted to APCI.

TASK 2 — Slurry Catalyst Improvement

2.1. Development of Wax Analysis Procedure.

We have continued work on an analytical technique for product wax ($C_{12}-$) collected in the high temperature trap (fixed bed) or accumulated in the reactor (slurry) during catalyst testing. A new Varian 3400 series gas chromatograph, equipped for capillary chromatography, has been received and installed. A Hewlett-Packard 3393A integrator is used to integrate and plot the detector signal from the Varian 3400. Data (peak areas and retention times) are transferred to an IBM-PC from the HP3393A for further calculations. An identification program has been written and tested which assigns a class and carbon number to each peak in the sample trace. The program also calculates the weight fraction of each component in the sample and estimates the weight recovery from the analysis. The output of the program is used to incorporate analyzed wax into the existing mass balance programs. The new system has been tested using existing organic standards for hydrocarbons and oxygenates with a 0.32-mm ID $\times$ 30-m DB-5 column (J&W Scientific) used for organic product analyses on the Perkin-Elmer Sigma 1 GC. The separation and response factors for the standards were found to be acceptable.

The work in the past quarter has concentrated on selection of a column and solvent for the wax analysis. Using the most promising column/solvent, the best analysis conditions (sample size and dilution, temperature program) were determined by a series of injections using standards and typical reactor waxes.

Four columns have been tested using a wax standard. A 0.32-mm ID $\times$ 15-m DB-1 (methylsilicone, Varian Associates) and a 0.32-mm ID $\times$ 10-m DB-5 (5 % phenylmethyl, J&W Scientific) were tested. These columns have relatively low maximum temperatures (320 °C). A megabore 0.53-mm

ID-10-m RSL-150 (bonded polydimethylsiloxane, Alltech Associates) and an Al-clad 0.25-mm ID-15-m Supercap (bonded methylsilicone, Quadrex Corp.) were also tested. These two columns have higher maximum temperatures (350 and 425 °C, respectively) and thin films (0.25 and 0.1 μm , respectively), which are more suitable to analysis of high molecular weight samples.

The wax standard used to evaluate these columns contained selected C_{16} - C_{44} *n*-paraffins and 1-eicosene (C_{20}) in approximately equal weight fractions, dissolved in CS_2 to about 6 *mg/ml*. Each of the four columns tested provided good separation of the components in the standard, but the analyses all showed a decrease in sensitivity for the higher carbon number components. The DB-1 and DB-5 columns were removed from consideration as they showed no significant advantages over the other two columns and have limited temperature ranges as well.

The RSL-150 and Supercap columns were further tested using product wax collected from a fixed bed run (FA-63-0418-3). The wax, with approximately 10 weight % *n*-hexadecane (C_{16}) added as an internal standard, was dissolved to about 6 *mg/ml* in CS_2 . Gentle warming was required for the wax to dissolve completely. The presence of the internal standard permits absolute weight fractions to be calculated directly from the peak areas and response factors of a given sample.

The absolute weight fraction is given by:

$$x_j = \frac{A_j}{A_s} \cdot \frac{W_s}{W_w R_j} \quad (1)$$

where A_j and A_s are the peak areas of component j and the internal standard, respectively, R_j is the response factor of component j , W_s and W_w are the weights of internal standard and wax dissolved in the sample (g), and x_j is the weight fraction of component j in the wax. The response factors are calculated on a weight basis from standards as $R_j = A_j x_s / A_s x_j$, where R_s is clearly unity.

The weight fraction of wax not detected is given by:

$$x_U = 1 - \sum_{i=1}^N x_i \quad (2)$$

where N is the number of detected components in the wax sample and x_U is the fraction of unanalyzed wax.

The RSL-150 column was able to give good separation and peak resolution up to C_{50} - C_{55} , where the column reached its maximum temperature. An example chromatogram of an RSL-150 analysis of high pressure trap product from run FA-63-0418-5 is shown in Fig. 1. Typically, 60-65 % of the sample was eluted from the column and detected during the preliminary wax analysis tests. The Supercap column can be used up to the maximum temperature limit of the GC (400 °C), and eluted peaks corresponding to the C_{65} - C_{70} range. Approximately 40 % of the sample was recovered during the analysis, which is less than the recovery from the RSL-150 analysis. The Supercap column is a narrow bore column (0.25-mm ID) and smaller sample sizes must be used than with the RSL-150. This made minor peaks difficult to detect such that the sum of the minor peak areas, which represent a significant portion of the total peak area, were not included accurately into the analysis. The exclusion of the minor peaks is believed to be the major reason for the lower recovery, in spite of the higher carbon number analysis of the Supercap column. Also, the absolute weight fractions were generally less than with the RSL-150 column.

The RSL-150 column was selected to perform the wax analysis, and a procedure was developed to give acceptable analyses of the product wax samples from fixed bed run FA-63-0418. A shift in baseline occurs from temperature programming the column, particularly at higher carbon numbers. Large injection volumes (1.5 μ l) and concentrated samples (12 mg/ml CS_2) were used to decrease the baseline shift relative to the peak areas. The sample was warmed to approximately 40 °C to completely dissolve the wax, and was drawn into a cool syringe (ca. 25 °C) immediately before injection. A simple column temperature program, 35 - 320 °C @ 4 °C/min, was found to give good separation of the sample over the range of the column. The conditions selected for the wax analysis procedure are summarized in Table 1.

In order to assess the reproducibility of the analysis and determine the effect of wax analysis on the product distribution, four injections of wax standard and two injections of wax from run FA-63-0418-5 were made and compared. This run was selected since the weight percent of wax collected was high, and the product distribution (excluding wax) did not show large deviations from Schulz-Flory. The reproducibility of the wax standard was good, less than 2 % relative deviation for all components in the standard excluding C_{20} . With the large component concentrations in the

standard, the C₂₀ olefin and paraffin did not separate well, causing errors in the two peak areas. In a real wax, the component concentrations are much lower, and the column can separate the olefin and paraffin peaks up to about C₂₇. The response factors ranged from 0.93–1.0, with the response factors generally decreasing with carbon number, and were correlated with an exponential fit (*i.e.*, $R_j = ae^{bj}$). The correlation was used to calculate response factors for all components greater than C₁₆; for components less than or equal to C₁₆, the response factors were assumed to be unity. The response factors and their percent relative deviations are given in Table 2.

The averages and percent relative deviations for the fixed bed wax analyses are given in Table 3. Large deviations occur for the isomers, where the results are obtained from the sum of several small peaks. This also occurs for *n*-decane, which is also present only in small quantities (0.035 %). Lumping the results reduces the errors arising from smaller peaks, decreasing the relative deviations to less than 4 % for the C₉–C₂₅, C₁₂–, and C₂₆– fractions. The large deviations in the C₅–C₁₁ fraction are due to the small amounts of these components in the wax.

The effect of analyzed wax on the lumped hydrocarbon distribution is shown in Table 4 for the analyses given in Table 3. The methane and C₂–C₄ fractions are not present in the wax sample, and only small changes in the numerical values occur. These changes are caused by the oxygenates present in the wax sample. Before analysis, any oxygenates present in the wax are classed as hydrocarbons, which lowers the percentage of all fractions other than wax. After analysis, any oxygenates in the wax are excluded from the hydrocarbons, thus the percent of other fractions increase. The C₅–C₁₁ fraction also increases slightly after analysis of the wax, which is due to the small amount of C₁₀ and C₁₁ hydrocarbons in the wax as well as the exclusion of oxygenates from the hydrocarbon distribution. These two effects also cause a small decrease in the C₁₂+ (including wax) fraction. A large difference is seen in the C₁₂+ (excluding wax) fraction. Before the wax is analyzed, only small amounts of C₁₂+ products present in the organic liquid product appear in this fraction; however, including the wax analysis incorporates the major portion of the wax sample as C₁₂–.

An Anderson–Schulz–Flory plot of the total molar distribution is shown in Fig. 2. A distinct break in the plot occurs at the higher carbon numbers, giving $\alpha_{1-10} = 0.67$ and $\alpha_{11-} = 0.96$. The

slight negative deviation at C_8 - C_9 is due to evaporation of these products during sample handling, and the positive deviations at C_{45} are caused by errors in the analysis from baseline shift. A large negative deviation occurs in the C_{12} - C_{18} range. Compounds in this range are present in small quantities in both the organic liquid and wax analysis, and are thus susceptible to analytical errors. Also, these components may volatilize in the hot trap (wax collection) yet condense before reaching the ice trap (liquid collection) and not be thoroughly collected. The results obtained for this particular balance may not be representative of all our data. For example, the $C_{11} + \alpha$ value appears unrealistically high, although there was a large fraction of wax collected during this balance. Incorporating wax into the data of run FA-15-0278-1 gives $\alpha_{1-10} = 0.72$ and $\alpha_{11+} = 0.91$, which is a more reasonable result. The data for this run do not show the negative deviations in the C_{12} - C_{18} range, either. We are in the process of analyzing selected wax samples collected in previous runs, and will discuss the results in future reports.

2.2. Slurry Reactor Wax Withdrawal Studies.

We have attempted to improve the method of withdrawing accumulated product wax from the slurry reactors during catalyst tests. In the past, wax withdrawals were made by stopping the reactor stirrer and bypassing the reactor feed in order to allow the catalyst to settle from the slurry. After a short settling period, wax was withdrawn through a dipleg set at a preset height in the reactor. While this procedure was simple to implement and was generally reliable, our experience showed that this major disturbance to the reactor appeared to cause or accelerate catalyst deactivation. Allowing the wax to accumulate over multiple balances, as was done in run SA-05-2957 (Technical Progress Report for the period 1 October - 31 December 1988), caused other difficulties, as poor mass closures and inaccurate selectivities result from the unaccounted accumulation of wax.

Three methods have been tested which permit the withdrawal of accumulated wax at the end of each mass balance period with a minimum of interference to the catalyst: (1) wax withdrawal through a filter internal to the reactor, (2) wax withdrawal through a filter external to the reactor, which could be changed on-line if the filter became irreversibly plugged, and (3) withdrawal of

excess slurry to an external settling tank, with a return of catalyst to the reactor.

Experiments with both filter methods using 10 and 20 μm sintered plates were successful with slurries of toluene and < 325 mesh catalyst, and also worked when a hard paraffin wax (FT-300, Dura Commodities) was used without solids. However, when a slurry of FT-300 wax and 10 weight % (< 325 mesh) precipitated iron catalyst was tested at typical reaction conditions (250 °C, 1.48 MPa), the filters (both internal and external) became plugged with solids before any significant quantity of wax could be withdrawn. The filters were readily cleared by backflushing with helium, but continued to plug with repeated attempts to withdraw wax.

Withdrawal of excess slurry to an external settling tank was successful. Excess slurry was withdrawn through a dipleg to a 500 cc external settling tank. The catalyst was allowed to settle for about 45 minutes, and clear wax in the top portion of the settling tank was siphoned to a collection vessel. The concentrated slurry (~ 80 cc) remaining in the bottom of the settling tank was returned to the reactor by pressurizing to about 50 psi above the reactor pressure. After draining, the tank was rinsed once with 50–75 cc of *n*-hexane to remove any catalyst clinging to the walls of the settler, and this dilute slurry was also drained to the reactor. The procedure worked well, but small amounts of catalyst were found in the clear wax removed from the settling tank. The amount of catalyst in the wax is easily quantified by filtering the wax, and represents only a small fraction of the catalyst charged to the reactor. The procedure of slurry withdrawal and quantification of wax produced was adopted for future runs, and a schematic of the withdrawal system installed on both slurry reactors is shown in Fig. 3.

2.3. TASK 2.2 — Binder/Support Effect Research.

2.3.1. Tests of SiO₂-Containing Catalysts.

A series of three SiO₂-containing catalyst tests in fixed bed reactors has been completed. The catalysts were doubly promoted with Cu and K (100 Fe/5 Cu/4.2 K) and contained 8 (run FA-63-0418), 25 (FA-66-0548), and 100 parts SiO₂ per 100 parts Fe (FA-69-0668). The catalysts were ground and sized to 30/60 mesh, and diluted with glass beads of the same mesh size range when loaded to the reactor. Catalyst reduction was performed *in situ*, using CO as the reductant for

12 h at 280 °C. The runs included at least five mass balances, at 220, 235, and 250 °C, 2 and 4 $Nl/g\text{-cat}\cdot h$, and 1.48 and 2.96 MPa . Only a single balance was conducted at high pressure, and all balances were made using a nominal $(H_2/CO) = 1$ synthesis gas.

Six balances were performed during run FA-63-0418, and the results of this run are summarized in Table 5. The activity of the 100 Fe/5 Cu/4.2 K/8 SiO_2 -containing catalyst was very high, and was superior to all catalysts tested thus far. The (H_2+CO) conversion at 220 °C was 62.1 % (balance 4), increasing to 76.7 % at 235 °C (balance 1) at the same pressure and space velocity (1.48 MPa , 2 $Nl/g\text{-cat}\cdot h$). Increasing the space velocity to 4 $Nl/g\text{-cat}\cdot h$ gave (H_2+CO) conversions of 52.8 and 65.1 % at 235 and 250 °C, respectively. Catalyst deactivation occurred when the pressure was increased to 3.0 MPa in balance 5. This balance was made at the same (P/SV) as balance 1, yet the (H_2+CO) conversion was only 42.7 % as compared to the 76.7 % obtained in balance 1. A reproducibility check using the conditions of balance 1 was performed during balance 6, and the (H_2+CO) conversion was only 44.8 %. This conversion is comparable to that of balance 5, and indicates that although the catalyst deactivated at high pressure, the deactivation did not continue after the pressure was reduced.

The weight percent methane in the hydrocarbon products was low at all conditions tested using the 8 parts SiO_2 catalyst. The hydrocarbon distribution at 220 °C, 1.48 MPa , 2 $Nl/g\text{-cat}\cdot h$ (balance 4) was 2.77 (CH_4), 16 (C_2-C_4), 15.4 (C_5-C_{11}), and 65.8 % ($C_{12}+$). Raising the temperature to 235 °C (balance 1) increased the methane fraction slightly, to 3.47 %, with a decrease in $C_{12}+$ products to 60 %, and at 250 °C (4 $Nl/g\text{-cat}\cdot h$, balance 3) methane continued to increase to 3.69 %. No significant effect was seen with space velocity (2 and 4 $Nl/g\text{-cat}\cdot h$) at 235 °C, 1.48 MPa (balances 1 and 2) on the weight percent hydrocarbon distribution.

Five mass balances were performed during the test of the 100 Fe/5 Cu/4.2 K/25 SiO_2 catalyst, run FA-66-0548. The results of this run are given in Table 6. The (H_2+CO) conversion at 220 °C (1.48 MPa , 2 $Nl/g\text{-cat}\cdot h$, balance 4) was 31.1 %, increasing to 55 % at 235 °C and 67.6 % at 250 °C. Doubling the space velocity to 4 $Nl/g\text{-cat}\cdot h$ at 235 °C decreased the (H_2+CO) conversion to 38.5 %. The 25 parts SiO_2 catalyst deactivated mildly at high pressure. During balance 5, at 2.96 MPa (235 °C, 4 $Nl/g\text{-cat}\cdot h$) the (H_2+CO) conversion was 48.1 %, compared to the 55.0 %

conversion obtained during balance 1 at the same temperature and (P/SV) ratio. No repeat of conditions was made during this run.

The weight percent hydrocarbon distribution obtained from this catalyst followed the expected trends with process conditions. At 235 °C, 1.48 MPa, 2 $Nl/g\text{-cat}\cdot h$ (balance 1) the distribution was 5.64 (CH_4), 22.5 ($C_2\text{-}C_4$), 15.2 ($C_5\text{-}C_{11}$), and 56.4 % ($C_{12}+$). Little change was seen in the distribution as the space velocity was increased to 4 $Nl/g\text{-cat}\cdot h$ during balance 2. Increasing the pressure to 2.96 MPa at the higher space velocity (balance 5) decreased methane to 4.07 % with slight changes in the other product fractions. The percentage of methane in the hydrocarbon products increased with temperature: 4.88, 5.64, and 8.07 % at 220, 235 (balance 1), and 250 °C, respectively. The $C_2\text{-}C_4$ products were higher (30 %) at 250 °C, and the temperature also caused some shifting between the $C_5\text{-}C_{11}$ and $C_{12}+$ product fractions.

The results of the run using 100 Fe/5 Cu/4.2 K/100 SiO_2 catalyst (run FA-69-0668) are summarized in Table 7. The activity of this catalyst was relatively low, 15.8 % (H_2+CO) conversion at 220 °C (1.48 MPa, 2 $Nl/g\text{-cat}\cdot h$, balance 3), increasing to 29.1 and 35.2 % at 235 and 250 °C (balances 1 and 3), respectively. At higher space velocity (4 $Nl/g\text{-cat}\cdot h$, balance 2) and 235 °C, the (H_2+CO) conversion was only 22 %. With high SiO_2 content, the catalyst appeared to be less prone to deactivation at high pressure. A repeat of the conditions used during balance 1 (235 °C, 1.48 MPa, 2 $Nl/g\text{-cat}\cdot h$) was made in balance 5, and the (H_2+CO) conversion dropped slightly from 29.1 to 25.7 %. During balance 6, the pressure was increased to 2.96 MPa, holding (P/SV) constant, and the (H_2+CO) conversion was 29.4 %, which is in good agreement with the balance 1 conversion.

The effect of temperature on weight percent hydrocarbon distribution can be seen in balances 4 (220 °C), 1 (235 °C), and 3 (250 °C) at 1.48 MPa and 2 $Nl/g\text{-cat}\cdot h$. The methane and $C_2\text{-}C_4$ fractions increase with temperature, from 4.58 and 15.8 % (220 °C) to 5.19 and 17.2 % (235 °C) and 5.90 and 18.6 % (250 °C). The fraction of high molecular weight compounds ($C_{12}+$) decreased correspondingly with an increase in temperature. An increase in space velocity at 235 °C, 1.48 MPa from 2 (balance 1) to 4 $Nl/g\text{-cat}\cdot h$ (balance 2) decreased the percentages of lighter products. Methane decreased from 5.19 to 4.44 %, and $C_2\text{-}C_4$ decreased from 17.2 to 14.9 % as the space

velocity increased. Little change was seen in selectivity between balances 1 and 5, run at the same conditions (235 °C, 1.48 MPa, 2 $\text{Nl/g-cat}\cdot\text{h}$). As pressure was increased at constant (P/SV) to 2.96 MPa between balances 1 or 5 and balance 6, the product distribution shifted towards the higher molecular weight compounds. For example, methane decreased from 5.19 % (balance 1) to 4.51 % (balance 6). The distribution at higher pressure was similar to that obtained at lower pressure (1.48 MPa) and the same space velocity (4 $\text{Nl/g-cat}\cdot\text{h}$).

A comparison of the three SiO_2 -containing catalysts is made in Table 8, which shows abbreviated activity and selectivity results for each run at similar operating conditions. Results from the test of Ruhrchemie LP 33/81 catalyst, reduced using CO (280 °C, 8 h, run FB-99-3477, reported in the Technical Progress Report for the period 1 October – 31 December 1987) and a 100 Fe/3 Cu/0.2 K catalyst (run FA-25-2447, reported in the Technical Progress Report for the period 1 July – 30 September 1987) are also shown. The catalyst containing 8 parts SiO_2 is clearly the most active catalyst at all conditions tested. At 235 °C, 1.48 MPa, 2 $\text{Nl/g-cat}\cdot\text{h}$, the ($\text{H}_2 + \text{CO}$) conversion decreased 76.7, 55.0, and 29.1 % as the SiO_2 content increased 8, 25, 100 parts per 100 parts Fe. A decrease in activity with SiO_2 concentration was expected since the content of active metal (Fe) decreases. The 8, 25, and 100 parts SiO_2 -containing catalysts contain 60, 50, and 39 % Fe by weight on an unreduced basis; however, the increase in ($\text{H}_2 + \text{CO}$) conversion exceeds that due to the higher Fe concentration. In Fig. 4, the ($\text{H}_2 + \text{CO}$) conversion is plotted against space velocity ($\text{Nl/g-Fe}\cdot\text{h}$) on a per gram Fe basis to account for the difference in iron content. The 8 SiO_2 catalyst remains more active than the other SiO_2 -containing catalysts when the metal content is considered.

The activity of the 8 parts SiO_2 catalyst was also greater than the activity of the Ruhrchemie LP 33/81 catalyst and the precipitated 100 Fe/3 Cu/0.2 K catalyst. The Ruhrchemie catalyst is believed to be similar in composition to the 25 parts SiO_2 catalyst prepared under this investigation. According to Dry (1981), the Ruhrchemie catalyst has the composition 100 Fe/5 Cu/5 K_2O /24 SiO_2 , yet there were differences between the commercial catalyst and our catalyst, depending on operating conditions. At 220 °C, 1.48 MPa, 2 $\text{Nl/g-cat}\cdot\text{h}$, the ($\text{H}_2 + \text{CO}$) conversions obtained using the Ruhrchemie catalyst was 37.9 %, compared to 31.1 % for our 100 Fe/5 Cu/4.2 K/25 SiO_2

catalyst. At higher temperatures, the conversions obtained from the Ruhrchemie catalyst were 43.7 % (235 °C) and 60.6 % (250 °C), less than that obtained from the 25 parts SiO₂ catalyst, 55.0 (235 °C) and 67.6 % (250 °C). For comparison, the (H₂+CO) conversions for the Ruhrchemie and 100 Fe/3 Cu/0.2 K catalysts are also plotted in Fig. 4.

The selectivity of the 100 Fe/5 Cu/4.2 K/8 SiO₂ catalyst was better than that of the other SiO₂-containing catalysts, as less methane and C₂-C₄ and more C₁₂+ products were formed using 8 parts SiO₂. At 235 °C, 1.48 MPa, 2 NL/g-cat·h, the 8 parts SiO₂ catalyst produced 2.77 % methane and 16.0 % C₂-C₄ products, while 4.88 (CH₄) and 23.1 % (C₂-C₄) were formed from the 25 parts SiO₂ catalyst and 4.58 (CH₄) and 15.8 % (C₂-C₄) were formed from the 100 parts SiO₂ catalyst. The more desirable selectivity was apparent at all process conditions, for example, at 250 °C, the weight percent methane was 3.69, 8.07, and 5.90 % at SiO₂ levels of 8, 25, and 100 parts per 100 parts Fe.

The Ruhrchemie LP 33/81 and 100 Fe/3 Cu/0.2 K catalysts form more methane and C₂-C₄ products than the SiO₂-containing catalysts. In comparison to the catalyst containing 8 parts SiO₂, at 250 °C the methane and C₂-C₄ fractions were 7.6 and 32 % (Ruhrchemie LP 33/81), and 10.3 and 36.8 % (100 Fe/3 Cu/0.2 K), which are significantly higher than the silica-containing catalyst, 3.69 and 16.0 %. The C₁₂+ fractions were also higher using the 100 Fe/3 Cu/4.2 K/8 SiO₂ catalyst: 20, 32.4 and 67.9 % at 235 °C with the Ruhrchemie, 100 Fe/3 Cu/0.2 K, and 100 Fe/5 Cu/4.2 K/8 SiO₂ catalysts, respectively.

2.3.2. Run FA-73-0828 (100 Fe/5 Cu/4.2 K/8 Al₂O₃).

Run FA-73-0828 was a fixed bed test of the 100 Fe/5 Cu/4.2 K/8 Al₂O₃-containing catalyst. 3.4 g of the catalyst (30/60 mesh) were loaded to the reactor, diluting the catalyst with glass beads of the same mesh size range to obtain an overall ratio of 8 parts glass per part catalyst, by volume. The catalyst was reduced at 280 °C for 12 h using CO reductant before exposure to synthesis gas. Six material balances were performed during this run, and the results are summarized in Table 9.

The initial activity of this catalyst was lower than expected, but the catalyst became more active with time. At 7.5 h the gas contraction was measured at 29.8 %, which increased steadily

to 53.4 % by 23 h, after which the contraction was relatively stable. From about 6 to 54 h on stream, the reactor was held at a set of constant conditions (235 °C, 1.48 MPa, 2 NL/g-cat·h). During the first balance, the (H₂+CO) conversion was measured at 75.1 %, which is quite high and comparable to the conversion obtained at the same conditions with the catalyst containing silica in the same nominal proportion, 76.7 % (run FA-63-0418-1). Raising the space velocity to 4 NL/g-cat·h (balance 2) decreased the (H₂+CO) conversion to 47.0 %, and an increase in temperature to 250 °C (balance 3) at the higher space velocity gave a conversion of 57.8 %. These conversions are also similar to the 8 parts SiO₂ catalyst: 52.8 (balance 2) and 65.1 % (balance 3) at 235 and 250 °C (4 NL/g-cat·h). The catalyst deactivated after balance 3 (250 °C) and the conversions obtained during balance 4 were lower than expected. A repeat of the conditions of balance 1 during balance 5 (235 °C, 2 nl/g-cat·h) showed a significant decrease in conversion from 75.1 to 42.9 %.

At 235 °C, 4 NL/g-cat·h, 1.48 MPa (balance 2) the weight percent hydrocarbon distribution was 4.19 (CH₄), 17.4 (C₂-C₄), 18.4 (C₅-C₁₁), and 60.0 % (C₁₂+). An increase in temperature to 250 °C (balance 3) increased the percent of methane to 4.91 % and decreased the C₁₂+ fraction to 55.7 %. A mild shift in the distribution was also seen during balances 1 and 4, where the temperature was increased from 220 to 235 °C at 2 NL/g-cat·h, increasing methane from 4.22 to 4.83 % and decreasing C₁₂+ from 59.1 to 57.5 %. Little change in the hydrocarbon distribution was seen as the catalyst deactivated between balances 1 and 5. The deactivated catalyst was slightly more selective towards lighter products, with an increase in the C₂-C₄ fraction from 18.4 to 19.6 %.

The product distribution from the 8 Al₂O₃ catalyst was similar to that of the 8 SiO₂ catalyst, with the alumina catalyst producing slightly higher methane and C₂-C₄ fractions with correspondingly lower C₅+ fractions than the silica catalyst. For example, at 235 °C, 1.48 MPa, 2 NL/g-cat·h (balance 1 for both runs) the percent methane was 3.47 and 4.83 % and the percent C₁₂+ was 60.0 and 57.5 % for the SiO₂- and Al₂O₃-containing catalysts. Similar differences were observed for all process conditions tested.

2.4. TASK 2.4 — Activation/Reduction Procedure Research.

2.4.1. Run FB-25-0098 (100 Fe/3 Cu/0.2 K).

Run FB-25-0098 (100 Fe/3 Cu/0.2 K) was a repeat of run FB-25-2857 (Technical Progress Report for the Period 1 October – 31 December 1987), using a catalyst reduced in CO at 250 °C for 24 h. Following reduction, the catalyst was subsequently subjected to a fixed set of operating conditions (250 °C, 1.48 MPa, (H₂/CO) = 1, nominal) for approximately 119 h on stream, during which two mass balances were completed. The results obtained during these two balances are summarized in Table 10. Our previous results from the 8 h CO reductions showed that the 250 °C reduction led to a more active and stable catalyst than reduction at 280 °C; however, using 24 h reductions, the catalyst reduced at 250 °C deactivated much more rapidly than the catalyst reduced at 280 °C. The retest was scheduled to verify this result.

A stability plot, (H₂+CO) conversion versus time at conditions, is shown in Fig. 5 for the 250 and 280 °C reductions of 8 and 24 h duration. The catalyst tested during run FB-25-0098 again deactivated rapidly, as was found in the previous test using the same reduction conditions. The deactivation trends of both tests were similar, thus the 250 °C, 24 h reduction must lead to a catalyst with poor stability behavior.

The selectivity results obtained in each of the two tests using 250 °C, 24 h reductions were also similar. In the first mass balance at approximately 71 h on stream, the weight percent hydrocarbon distribution was 7.48 (CH₄), 28.3 (C₂-C₄), 36.9 (C₅-C₁₁), and 27.3 % (C₁₂+), which favors lower molecular weight products slightly more than in the previous test which produced 5.54 (CH₄) and 20.6 % (C₂-C₄) of the lighter products. As the catalyst deactivated, more methane and C₂-C₄ products were formed, increasing to 8.22 (CH₄) and 29.1 % (C₂-C₄) in balance 2 at approximately 119 h on stream. This trend was also observed in the original test using these reduction conditions.

2.5. Slurry Reactor Kinetic Studies.

2.5.1. Run SB-07-0458 (100 Fe/0.3 Cu/0.5 K).

This was the first run made in the new Slurry B reactor unit. The precipitated 100 Fe 0.3 Cu 0.5 K catalyst was reduced *in situ* using H₂ as the reductant (280 °C, 0.77 MPa for 24 h). The

catalyst ($< 325\ mesh$) was suspended in a FT-300 wax to obtain a 10 weight % catalyst slurry. The slurry withdrawal dipleg was preset to give a static slurry volume of 375 cc. Ten material balances were performed during the run, and the run was voluntarily terminated after 458 h on stream. The range of process conditions used during the run are summarized in Table 11, and the results obtained are summarized in Table 12.

At 4 h on stream, the inlet feed line had to be repaired due to a block that appeared following the withdrawal of excess wax from the reactor after catalyst reduction. No other major operational problems were encountered during the run. The major events of Run SB-07-0458 are summarized in Table 13.

The initial activity of the catalyst was low, which is consistent with previous observations made in fixed bed reactors with 100 Fe/3 Cu/0.2 K catalyst reduced using H_2 . The ($H_2 + CO$) conversion obtained during balance 1 was 24.8 %, which is comparable with the 26.0 % conversion obtained in the fixed bed test with 100 Fe/3 Cu/0.2 K catalyst reduced under similar conditions (280 °C for 24 h, run FB-25-3227, Technical Progress Report for the period 1 October - 31 December 1987). The catalyst appeared to have become more active with time on stream, as is evident from the ($H_2 + CO$) conversions obtained in balances 1 and 9 at 250 °C, 1.48 MPa, (H_2/CO) = 1 and a nominal space velocity of 2 $Nl/g\text{-cat}\cdot h$. During balance 1 (approximately 45 h on stream) the ($H_2 + CO$) conversion was 24.8%, while during balance 9 (approximately 428 h on stream) the conversion had increased to 35.5 %. Catalyst activity improved following balance 4, during which a 0.67 (H_2/CO) feed ratio was used, while a 1.0 (H_2/CO) feed ratio was used in the previous three balances. During the period of low catalyst activity (balances 1 through 4), the ($H_2 + CO$) conversion increased from 24.8 % (balance 1) to 30.8 % (balance 3) as temperature increased from 250 °C to 265 °C, whereas the increase was from 42.5 % (balance 5) to 70.8 % (balance 7) once the catalyst became active, although the differences in space velocity and (H_2/CO) feed ratio may have influenced the results.

The catalyst selectivity shifted towards lower molecular weight products with an increase in temperature, once the catalyst became active (i.e. following balance 4). For example, the distribution at 235 °C, 1.48 MPa, 1 $Nl/g\text{-cat}\cdot h$, (H_2/CO) = 0.67 (nominal) during balance 8

was 2.11 (CH₄), 8.94 (C₂-C₄), 16.25 (C₅-C₁₁), and 73.01 % (C₁₂⁺), as compared to 2.76 (CH₄), 11.89 (C₂-C₄), 19.97 (C₅-C₁₁), and 65.80 % (C₁₂⁺) at 250 °C, and 3.25 (CH₄), 11.45 (C₂-C₄), 20.57 (C₅-C₁₁), and 64.97 % (C₁₂⁺) at 265 °C. The effect of temperature on selectivity at other conditions were not consistent with the above example, probably because of differences in catalyst activity. An increase in space velocity from 1 to 2 *Nl/g-cat·h* also caused the distribution to shift towards lower molecular weight products. This was evident from the distribution during balance 7 (1 *Nl/g-cat·h*, (H₂/CO) = 0.67, 265 °C, 1.48 *MPa*) compared to the distribution at balance 6 at the same nominal process conditions but with a space velocity of 2 *Nl/g-cat·h*. The distribution during balance 7 was 3.36 (CH₄), 13.53 (C₂-C₄), 21.07 (C₅-C₁₁), and 62.36 % (C₁₂⁺), as compared to 3.25 (CH₄), 11.45 (C₂-C₄), 20.57 (C₅-C₁₁), and 64.97 % (C₁₂⁺) during balance 6. Similar shifts in the distribution were observed at other conditions. As expected, fewer low molecular weight products were produced at 2.96 *MPa* than at a lower pressure of 1.48 *MPa* (balance 10 versus balance 6).

Wax withdrawals were made following catalyst reduction, and at the end of each mass balance period, using the external slurry settling tank. The quantities of wax and catalyst removed during these withdrawals after gravity settling of catalyst are shown in Table 14. The weight of catalyst removed during each withdrawal was less than 1 weight % of the wax for most cases. As can be seen from Table 14, wax production was much higher once the catalyst became active. The poor solids recovery (76 %) is due to losses during handling of the slurry at the end of the run. Several filtering techniques were tried to separate the catalyst from the wax in order to quantify the solids and wax fractions. Some solids were lost during each of these attempts, leading to the poor solids recovery.

2.5.2. Run SA-07-0468 (100 Fe/0.3 Cu/0.5 K).

Slurry run SA-07-0468 was made using precipitated 100 Fe/0.3 Cu/0.5 K catalyst reduced *in situ* using CO as the reductant (280 °C, 0.79 *MPa*, 16 *h*). The catalyst (< 325 *mesh*) was suspended in FT-300 wax to obtain a 10 weight % catalyst slurry. The slurry withdrawal dipleg was preset to give a static slurry volume of 385 cc. Eleven material balances were performed during the run,

before being voluntarily terminated after 466 h on stream. The balances were made over a range of process conditions, given in Table 15, and the results obtained are summarized in Table 16.

Beginning at about 20 h on stream, the H₂ mass flow controller began behaving erratically, giving lower than expected flowrates. To achieve the desired flowrates and feed ratios, the feed was switched from pure gas to premixed gas at about 52 h on stream. At about 78 h on stream, an improperly mixed feed gas cylinder containing approximately 95 % H₂ was installed, exposing the catalyst to nearly pure H₂ for about 1 h before the problem was discovered and corrected. The exposure to H₂ did not appear to harm the catalyst, as the catalyst activity (conversions and contraction) of the catalyst before and after the interruption was comparable. No other major operational problems were encountered during the run. The major events of run SA-07-0468 are summarized in Table 17.

The activity of the catalyst during balance 1 was high, (250 °C, 1.48 MPa, (H₂/CO) = 1.0, 2), and comparable to the fixed bed test of a similar catalyst composition (100 Fe/3 Cu/0.5 K, run FA-27-2557, Technical Progress Report for the period 1 July - 30 September 1987) at the same nominal conditions. During the test in the fixed bed, the (H₂+CO) conversion was 70.4 %, as compared to the 74.8 % obtained in the slurry test. Catalyst deactivation occurred when the temperature was increased to 265 °C between balances 2 and 3 (at 1.48 MPa, (H₂/CO) = 1.4 NL/g-cat·h). The (H₂+CO) conversion dropped from 58.4 % in balance 2 (250 °C) to 55.5 % in balance 3 (265 °C), in spite of the 15 °C temperature increase. In later balances using 0.67 (H₂ CO) feed gas, the increase in temperature from 250 to 265 °C also did not significantly increase conversion. In balances 8 (250 °C) and 9 (265 °C) the (H₂+CO) conversions increased only slightly from 24.0 to 28.2 %. The catalyst was severely deactivated by balance 10, which was a repeat of the conditions used during balance 1 (250 °C, 1.48 MPa, 2 NL/g-cat·h, (H₂ CO) = 1.0). The conversion dropped from 74.8 % to 17.4 % between the two balances.

Increases in temperature shifted catalyst selectivity to lower molecular weight products. For example, the distribution at 235 °C, 1.48 MPa, 1 NL/g-cat·h, (H₂/CO) = 0.67 (nominal) during balance 6 was 1.99 (CH₄), 11.0 (C₂-C₄), 12.5 (C₅-C₁₁), and 74.6 % (C₁₂+, as compared to 2.46 (CH₄), 12.8 (C₂-C₄), 19.5 (C₅-C₁₁), and 65.4 % (C₁₂+) at 250 °C (balance 7). Similar shifts in the

distribution were observed at other conditions, although catalyst deactivation may have influenced the results. Comparisons of balances 1 and 10 shows the effect deactivation may have on selectivity at 250 °C, where the deactivated catalyst produced fewer molecular weight products (4.54 % CH₄ and 17.3 % C₂-C₄) than the more active catalyst at the same nominal process conditions during balance 1 (6.86 % CH₄ and 22.3 % C₂-C₄). The shift in lower molecular weight products changed the percentage of the C₅-C₁₁ fraction, while the C₁₂+ products remained constant between the two balances.

Wax withdrawals were made following catalyst reduction, and at the end of each mass balance period, by removing excess accumulated slurry from the reactor to the external settling vessel. After separation by settling, the wax and trace quantities of catalyst were quantified, and are shown in Table 18 for each withdrawal. In all cases, the weight of catalyst removed with the wax (after settling) was small, less than 2 weight % of the wax.

2.5.3. Run SA-25-3657 (100 Fe/3 Cu/0.2 K).

Run SA-25-3657 was performed to test the precipitated 100 Fe/3 Cu/0.2 K catalyst under a variety of process conditions. Excess purified *n*-octacosane (C₂₈, Humphry Chemical) was loaded with catalyst (< 325 mesh) into the reactor prior to reduction, and the catalyst was reduced *in situ* with CO at 280 °C, 0.79 MPa for 24 h. Following reduction, the excess wax was withdrawn from the reactor to the preset static slurry volume of 478 cc. Eight material balances were made during this run, which was terminated voluntarily after 430 h of operation. The process conditions used during the run are given in Table 15, and the results obtained in each of the eight balances are summarized in Table 19.

A power loss occurred at about 129 h on stream, causing a flow interruption to the reactor. The reactor also cooled from 235 to 80 °C. Power was restored after 5 h, and the reactor was brought to its original temperature over a 4 h period. The catalyst was deactivating prior to the power failure, and continued to deactivate once the run continued. The deactivation made it difficult to determine what effect the interruption had on catalyst performance. Table 20 lists the major events occurring during run SA-25-3657.

The initial catalyst activity was good, with an (H_2+CO) conversion during balance 1 (250 °C, 1.48 MPa, (H_2/CO) = 1, 2 $Nl/g\text{-cat}\cdot h$) of 83.0 %. The conversion obtained in the fixed bed test of this catalyst at the same nominal process conditions was 72.2 % (Technical Progress Report for the period 1 July – 30 September 1987). No signs of deactivation were observed before the end of period 1 (50 h on stream), but after the wax withdrawal and an increase in space velocity to 4 $Nl/g\text{-cat}\cdot h$ a sharp decline in activity occurred. Over the 46 h period these conditions were maintained, the gas contraction decreased steadily from 48 to 36 %. The process conditions of balance 1 were repeated during balance 4, by which time the (H_2+CO) conversion decreased from 83.0 to 28.5 %.

In all cases, feed gas with (H_2/CO) = 0.67 (nominal) gave product distributions with lower weight percents of methane. In addition, the lower feed ratio produced larger amounts of high molecular weight products ($C_{12}+$). Methane was most abundant at 250 °C, 1.48 MPa, (H_2/CO) = 1, 2 $Nl/g\text{-cat}\cdot h$, where the weight percent methane was 9.4 %, more than twice that obtained at any other set of process conditions tested. These conditions were also best suited for production of gasoline range products ($C_5\text{--}C_{11}$). Catalyst deactivation may have skewed the selectivity trends of the run. For example, the methane and $C_2\text{--}C_4$ product fractions decreased as the catalyst deactivated between balances 1 and 4. The more active catalyst produced 9.31 % methane and 35.9 % $C_2\text{--}C_4$, as compared to 4.87 % and 21.7 %, respectively, during balance 4 at the same nominal process conditions (250 °C, 1.48 MPa, (H_2/CO) = 1, 2 $Nl/g\text{-cat}\cdot h$) after catalyst deactivation.

Wax was removed from the reactor at the end of each material balance. The reactor stirring and feed to the reactor were discontinued after purging the reactor for about 5 min with helium. The catalyst was allowed to settle for approximately 30 min , after which wax was withdrawn through a dipleg in the reactor at a preset height. The wax and catalyst withdrawals made during this run are summarized in Table 21.

2.5.4. Kinetic Parameter Estimation — Background.

The reactions of CO and H_2 in the slurry reactor may be approximated by two series-parallel reactions:

Fischer-Tropsch Synthesis

Water-Gas Shift

where m and n are the average number of hydrogen and carbon atoms, respectively, in the synthesis products, which may be experimentally determined by a thorough analysis of the reactor effluent.

These two reactions must be considered to account for both synthesis gas consumption and the (H_2/CO) usage in the reactor, and accurate balances may be written individually for both CO and H_2 . The material balances for CO and H_2 over a well mixed slurry reactor are:

$$\dot{n}_{\text{CO}}^i - \dot{n}_{\text{CO}} = w_{\text{cat}}(r_{\text{FTS}} + r_{\text{WGS}}) \quad (5)$$

$$\dot{n}_{\text{H}_2}^i - \dot{n}_{\text{H}_2} = w_{\text{cat}}[(1 + m/2n)r_{\text{FTS}} - r_{\text{WGS}}] \quad (6)$$

where $\dot{n}$ represents a molar flowrate (mols/h), r_{FTS} and r_{WGS} are the intrinsic rates of the Fischer-Tropsch and water-gas shift reactions ($\text{mols}/g\text{-cat}\cdot h$), w_{cat} is the weight of catalyst present in the reactor at the time of the balance on an unreduced basis ($g\text{-cat}$), and the superscript i denotes an inlet value.

Equations (5) and (6) were written assuming negligible mass transfer resistances. Bukur and Brown (1987) found that stirring speeds above 600 *rpm* were sufficient to minimize mass transfer resistance in a 0.3-*l* slurry stirred tank reactor using United Catalyst' C-73 fused iron catalyst. Satterfield and Huff (1982) and Nettelhoff *et al* (1985) also showed that 600 *rpm* limited mass transfer effects in 1-*l* slurry reactors. In the current investigation, stirring speeds of 1200 *rpm*, well above the minimum, were used during slurry reactor catalyst testing.

Measured values of the reaction rates can be calculated by rearranging Eqs. (5) and (6). In terms of process conditions and readily measured variables, the experimental rates are:

$$r_{\text{FTS}} = \frac{\psi}{2 + m/2n} s f_{\text{H}_2-\text{CO}} \quad (7)$$

$$r_{\text{WGS}} = \frac{1 + m/2n - U}{1 + U} \frac{\psi}{2 + m/2n} s f_{\text{H}_2-\text{CO}} \quad (8)$$

where f_{H_2+CO} is the fractional (H_2+CO) conversion, s is the inlet gas space velocity ($Nl/g\text{-cat}\cdot h$), U is the molar (H_2/CO) usage ratio, and $\psi = P_S/RT_S$ is the molar density of a perfect gas at standard conditions ($mols/l$).

Constants appearing in the rate expressions were estimated by minimizing the sum of squared residuals between the measured and expected reaction rates. Programs have been developed to perform these calculations, and a SAS package was also used to obtain parameter estimates.

2.5.5. Kinetic Parameter Estimation — Run SA-05-2957.

The data of slurry run SA-05-2957, reported in the Quarterly Progress Report for the period 1 October – 31 December 1987, were used to obtain kinetic expressions for both the FTS and WGS reactions. Only selected data taken during the run were used in fitting the rate constants. In the initial period of the run, the catalyst continued to become more active with time on stream, which was probably due to an incomplete initial CO activation at 250 °C for 8 h. Balance 6 of this run, at 265 °C, should have completed the activation of the catalyst, thus balances 1–6 were not included when estimating the kinetic parameters. Balance 12 was not included in the data set because of the poor mass closures obtained during this time period. The reactor had filled with wax by the end of balance 12, and the flows were unreliable.

Several FTS kinetic expressions were fit to the data, and the best correlation was obtained using an equation of the form:

$$r_{FTS} = \frac{k p_{CO} p_{H_2}^2}{p_{CO} p_{H_2} + b p_{H_2O}} \quad (9)$$

where $b(MPa)$ and $k(mols/g\text{-cat}\cdot h \cdot MPa)$ are temperature dependent constants, and p_j is the partial pressure of species j in the gas space of the reactor (MPa). This rate expression can be derived from either the carbide mechanism, or a combined enol/carbide mechanism with adsorption of water. Gas phase fugacities were estimated and the gas behavior was found to be very nearly ideal at all process conditions tested, justifying the use of partial pressures in the rate expression. The temperature dependence of b and k were presumed to follow the van't Hoff and Arrhenius equations:

$$b = \beta e^{\lambda/RT} \quad (10)$$

$$k = Ae^{-E/RT} \quad (11)$$

where A ($\text{mols/g-cat} \cdot \text{h} \cdot \text{MPa}$) and β (MPa) are the pre-exponential factors, E is the apparent activation energy of the synthesis reaction (kJ/mol), $R = 8.393 \cdot 10^{-3}$ ($\text{kJ/mol} \cdot \text{K}$), T is the absolute temperature of the reactor (K), and λ is a term related to the heats of adsorption on the catalyst surface (kJ/mol).

Only the data at 250 °C were sufficient to estimate b and k directly. Non-linear regression of all usable data at four temperatures (220, 235, 250, 265 °C) was used to estimate the four constants appearing in the rate equation (A , E , β , λ):

$$\begin{aligned} A &= 2.16 \cdot 10^8 \quad (\text{mols/g-cat} \cdot \text{h} \cdot \text{MPa}) & \beta &= 1.46 \cdot 10^{-9} \quad (\text{MPa}) \\ E &= 94.6 \quad (\text{kJ/mol}) & \lambda &= 96.3 \quad (\text{kJ/mol}) \end{aligned} \quad (12)$$

A parity plot of the experimental and expected rates appears in Fig. 6. Five of the eleven data points lie within 10 % of the expected values; only two points (balances 9 and 10) lie beyond 20 % of the prediction. Huff and Satterfield (1984) were also able to correlate their data from United Catalyst' C-73 fused iron catalyst using the same form of rate equation used here, and determined the activation energy E to be 83 kJ/mol . Activation energies for the FTS reaction are typically in the range 71–105 kJ/mol , and our value of 94.6 kJ/mol is in good agreement with other investigations.

The same set of data were used to fit expressions for the water-gas shift reaction rate. Two expressions were considered:

$$r_{\text{WGS}} = \frac{k_1(p_{\text{CO}}p_{\text{H}_2\text{O}} - p_{\text{CO}_2}p_{\text{H}_2}/K_P)}{p_{\text{CO}}p_{\text{H}_2} + bp_{\text{H}_2\text{O}}} \quad (13)$$

$$r_{\text{WGS}} = k_2 p_{\text{CO}} \quad (14)$$

K_P is the water-gas shift equilibrium constant, reported by Newsome (1980) as:

$$K_P = \exp(4577.8/T - 4.33) \quad (15)$$

Equation (13) represents mass action kinetics with the same denominator as Eq. (9), and has been used to correlate WGS reaction rates by others (Kuo *et al*, 1983). The values of β and λ

appearing in Eq. (10) for the term b in the denominator of Eq. (13) were assumed to be the same as for the FTS case, and estimates for A_1 and E_1 were found to be $1.4 \cdot 10^5 \text{ mols/g-cat}\cdot\text{h}$ and 53 kJ/mol , respectively, using non-linear regression of all usable data. A parity plot of the measured and expected rates appears in Fig. 7.

The simple first order in CO kinetics, Eq. (14), also gave a reasonable correlation of the experimental data, Fig. 8. The pre-exponential factor, A_2 was estimated to be $1.34 \cdot 10^{11} (\text{mols/g-cat}\cdot\text{h} \cdot \text{MPa})$, and the apparent activation energy E_2 was $126 (\text{kJ/mol})$. Feimer *et al* (1981) also correlated their data using a first order CO dependence on the WGS reaction rate, and reported an activation energy of 124 kJ/mol for the reaction over a Cu/K promoted, precipitated iron catalyst, which is essentially the same as our value.

2.6. Additional Fixed Bed Catalyst Tests.

2.6.1. Run FA-01-0128 (United Catalyst' C-73 Fused Iron).

Run FA-01-0128 was made using United Catalyst' C-73 fused iron catalyst, ground and sized to 170/230 *mesh*, as a retest of runs FA-01-1547 (Technical Progress Report for the period 1 April - 30 June 1987) and FA-01-1807 (Technical Progress Report for the period 1 July - 30 September 1987). In the two previous runs, catalyst deactivation occurred due to hot spots in the reactor caused by the high activity of the finely ground catalyst. Several improvements have been made in temperature control of the fixed bed reactors since the previous runs, and another attempt was made to get improved results from the 170/230 *mesh* catalyst.

Seven mass balances were performed during run FA-01-0128, and the results are summarized in Table 22. The catalyst initially showed lower than expected activity in balance 1, which improved in the later balances. In balance 1, the $(\text{H}_2 + \text{CO})$ conversion was 22.3 %, and at the same conditions in balance 6 (235°C , 0.79 MPa , $1.47 \text{ NI/g-cat}\cdot\text{h}$) the $(\text{H}_2 + \text{CO})$ conversion had increased to 33.2 %. A hot spot developed during balance 7, with a temperature difference of 29°C in the reactor; however, no hot spots were detected in the first 6 balances.

Catalyst activity in balances 2-6 were comparable to or better than in the previous runs at similar conditions. For example, the $(\text{H}_2 + \text{CO})$ conversions obtained in runs FA-01-1547 (bal-

ance 1) and FA-01-1807 (balance 1) at the same conditions as FA-01-0128-6 were 29.9 and 22.8 %, respectively. The most recent run showed a much greater tendency to form lower molecular weight products than was found before. The weight percent methane in the hydrocarbon products increased from 9.2 (FA-01-1547-1) and 3.51 % (FA-01-1807-1) to 15.3 % (FA-01-0128-6). A comparison of selected activity and selectivity results from the three 170 230 *mesh* fused catalyst runs appears in Table 23.

2.6.2. Run FA-15-0278 (100 Fe/1 Cu/0.2 K).

A test of a 100 Fe/1 Cu/0.2 K catalyst was made in run FA-15-0278. This catalyst was tested previously in run FA-15-2097 (Technical Progress Report for the period 1 July - 30 September 1987), with a slight modification in reduction procedure. The catalyst in run FA-15-2097 was reduced using CO at 280 °C for 8 h, while in the more recent run, the reduction duration was extended to 16 h. Five mass balances were performed during run FA-15-0278, and the results are given in Table 24.

The activity and selectivity during the first mass balance were in general agreement with those obtained in run FA-15-2097 at similar conditions (balance 5, 250 °C, 1.48 MPa, 2 *Nl/g-cat·h*). The (H₂+CO) conversion was 76.6 %, as compared to 78.9 % in the previous run. Hydrocarbon selectivity was also comparable: 8.53 and 11.4 (CH₄), 31.1 and 34.4 (C₂-C₄), 37.2 and 36.7 (C₅-C₁₁), and 23.2 and 17.4 % (C₁₂+) for runs FA-15-0278 and FA-15-2097, respectively.

In balances 2-5, the catalyst deactivated and the (H₂+CO) conversions dropped to unexpectedly low values. The conversions were 44.7, 26.2, and 24.2 % in balances 2-4. The (H₂+CO) conversions at similar conditions during run FA-15-2097 were 72.9 (balance 2), 49.6 (balance 3), and 39.4 % (balance 1). Balance 5 of the recent run was a repeat of the conditions of balance 1, and the (H₂+CO) conversion dropped from 76.6 to 58.9 %. The weight percent hydrocarbon distribution remained relatively constant between the two balances, regardless of the conversion level. No hot spots were detected during the run, and it is not clear what caused the rapid deactivation of catalyst after balance 1.

2.7. Catalyst Preparation and Characterization.

During the past quarter, we have completed the synthesis of the three alumina-supported precipitated iron catalysts that will be studied during this project. The principal focus of our research effort during this period was on characterizing the influence of silica and alumina binder/supports on the reduction and surface properties of these promoted catalysts. Information about comparative reduction behaviors of these materials and about the chemical/structural nature of surface sites has been obtained primarily from isothermal and temperature-programmed reduction (TPR) measurements and from X-ray photoelectron and Fourier Transform infrared (FT-IR) spectroscopic studies. Details of research progress in these areas are provided in the following sections.

2.7.1. Synthesis and Elemental Analysis of Alumina-Supported Precipitated Iron Catalysts.

The method used to prepare the three alumina-containing precipitated iron catalysts differed in certain details from that employed for preparation of the silica-supported materials described previously. The technique involves impregnation of the dried precipitate with an alcoholic solution of aluminum *sec*-butoxide, followed by hydrolysis of the impregnated alkoxide to alumina. A detailed description of the complete synthesis procedure that has been used for preparing all of the precipitated iron catalysts, both unsupported and supported, is contained in Appendix I. Much of this information has been provided piecemeal in various previous reports in this series, but for the sake of completeness has been compiled into a single narrative.

Aliquots from a single large (1 kg) batch of Fe-Cu precipitate were used to prepare each of the six supported catalysts. Nominal expected compositions of these materials were (in parts by weight): 100 Fe/5 Cu/4.2 K/ x SiO₂ and 100 Fe/5 Cu/4.2 K/ x Al₂O₃, where $x = 8, 25$, and 100. Actual elemental compositions were determined by atomic absorption spectroscopy, and are summarized in Table 25, where all results have been normalized to 100 parts by weight of Fe.

Analyzed contents of Fe, Cu, K and SiO₂ were quite close to the expected nominal compositions. It is apparent, however, that the maximum Al₂O₃ content that can be obtained by the alkoxide impregnation/hydrolysis technique employed for these preparations is less than 35 parts by weight per 100 parts of Fe. Attempts to increase the Al₂O₃ content by multiple impregnation steps

were unsuccessful, suggesting that pore filling had already occurred during the first impregnation. Measurements of surface areas and pore volume distributions for the three alumina-containing catalysts have not yet been completed and will be provided in a future report.

2.7.2. Reduction Studies of Supported, Precipitated. Catalysts.

Using techniques and equipment described in previous reports, both isothermal and temperature-programmed (TPR) reduction studies have been used to characterize reduction behaviors of the silica- and alumina-supported Fe/Cu precipitates. Figs. 9 and 10 illustrate the effect of increasing levels of silica binder on the TPR profiles in H_2 of precalcined (16 h in air at 300 °C) copper-promoted and copper-potassium-promoted iron catalysts. In both figures, the peak that occurs in each profile at ≤ 400 °C is due to almost simultaneous occurrence of the two processes $CuO \rightarrow Cu$ and $Fe_2O_3 \rightarrow Fe_3O_4$, while the peak(s) at > 400 °C are due to reduction of the latter to metallic iron. It is clear that increasing silica content decreases the ease of Fe_2O_3 reduction, but has relatively little effect on either CuO or Fe_3O_4 reduction. The effect is somewhat less pronounced when potassium promoter is present, since, as reported previously, potassium has a slight inhibitory effect on iron reduction. Isothermal reduction profiles, obtained at 300 °C (Figs. 11 and 12), confirm that the rate of the $Fe_3O_4 \rightarrow Fe$ reduction step decreases with increasing silica content, and that potassium promoter causes an additional decrease in the rate of reduction. Figs. 13-16 demonstrate that alumina binder/support also retards the rate of iron reduction, even at a nominal level of only 8 parts by weight (compare the profiles in Figs. 13 and 14 to profile (a) in Fig. 9). Unlike the situation observed with SiO_2 , the two catalysts containing 8 (7.7) and 25 (20.5) parts by weight of Al_2O_3 support exhibited virtually identical reduction behaviors.

The surface chemical state of certain of the supported catalysts, before and after reduction, has been investigated by X-ray photoelectron spectroscopy (XPS). Spectra in the Fe 2p, O 1s, and K 2p + C 1s regions are shown in Figs. 17-19 for a sample of the 100 Fe/5 Cu/4.2 K/8 SiO_2 catalyst that had been previously calcined in air for 16 h at 300 °C, and then treated in H_2 at 300 °C (spectra (a)), followed by exposure to 1 atm of a 2/1 H_2 CO mixture at 250 °C (spectra (b)). Figs. 17 and 18 demonstrate that, as observed previously for the unsupported 100

Fe/3 Cu/0.2 K catalyst, reduction of the silica-supported catalyst to metallic Fe^0 is incomplete following treatment in H_2 at 300 °C, and that subsequent exposure to a H_2/CO reaction mixture results in partial re-oxidation of surface Fe^0 . The high intensities of the K 2p peaks in Fig. 19 (for a material containing only 5 weight % K_2O) indicates that potassium promoter, under the influence of water generated during the H_2 reduction process, migrates on the catalyst surface to produce a uniform, thin layer that remains largely unchanged following subsequent H_2/CO reaction. This effect has been reported previously for the unsupported 100 Fe/3 Cu/0.2 K catalyst.

In contrast to the behavior of the unsupported catalysts investigated previously, reduction of 100 Fe/5 Cu/4.2 K/8 SiO_2 in CO at 300 °C does not lead to complete reduction of iron to the metallic state, as shown in Fig. 20. Exposure of the CO-reduced catalyst to a H_2/CO reaction mixture at 250 °C does not cause appreciable re-oxidation of surface iron. Fig. 21 illustrates that, unlike the case for reduction in H_2 , CO treatment leads to extensive deposition of surface carbon (spectrum (a)); the latter is removed during subsequent exposure to H_2/CO (spectrum (b)).

The reduction behavior and resulting surface chemical states determined by XPS for the 100 Fe/5 Cu/4.2 K/8 Al_2O_3 catalyst (Figs. 22-25) closely resemble those observed for the corresponding SiO_2 -containing material described above. With the alumina-supported catalyst, however, the mixture of iron oxidation states resulting from reduction in CO does not differ appreciably from that observed following treatment in H_2 . The C 1s region of the H_2 -reduced catalyst after exposure to H_2/CO is considerably more complex than that observed for silica-supported materials, and reveals the presence of at least three, and possibly four, distinguishable types of surface carbon following such treatment.

As observed during the isothermal and TPR reduction studies described above, XPS measurements also indicate that increasing concentration of SiO_2 support increases the difficulty of iron reduction to the metallic state, as shown in Fig. 26, where spectra for the 100 Fe/5 Cu/4.2 K/25 SiO_2 catalyst are presented. Not only is the extent of Fe^0 formation following reduction in either H_2 or CO at 300 °C much lower than that observed for the catalyst containing 8 parts SiO_2 (Figs. 17 and 20), but the overall intensity of the Fe 2p signal is decreased by 75 %. The latter observation is consistent with the increased level of SiO_2 at the catalyst surface. It should be noted

that the marked increase in intensity observed for the K 2p peaks following H₂ treatment of the 100 Fe/5 Cu/4.2 K/8 SiO₂ catalyst does not occur with the material containing 25 parts SiO₂, indicating that surface migration of potassium promoter is inhibited by increasing levels of SiO₂ binder/support.

2.7.3. Characterization of Silica Gel-Supported Impregnated Iron Catalysts.

Because the optical opacity of the precipitated iron catalysts prevents characterization by transmission infrared spectroscopy, we have continued our parallel investigation of a second series of 25 weight % Fe/SiO₂ catalysts. These have been prepared by co-impregnation of high surface area (300 m²/g) silica gel with appropriate amounts of Fe(NO₃)₃ and, when desired, Cu(NO₃)₂, followed by vacuum drying at 120 °C, impregnation with KHCO₃, if necessary, and subsequent calcination in air for 16 h at 300 °C. We have observed that certain reduction and surface properties of these impregnated catalysts closely resemble the corresponding behaviors of their precipitated counterparts.

An XPS spectrum (Fig. 30) for a sample of unpromoted 25 weight % Fe/SiO₂ that had been treated in O₂ at 300 °C and then cooled in O₂ to 25 °C demonstrates that, as observed previously for precipitated catalysts, such treatment leads to formation of Fe₂O₃. However, if the O₂ is removed by evacuation for 1 h at 300 ° and the sample is then cooled to 25 °C in vacuum, an XPS spectrum characteristic of a surface magnetite (Fe₃O₄) phase (Fig. 31) is observed. Treatment of the latter in H₂, even at 500 °C, leads to no detectable reduction of iron to the metallic state, as shown by the XPS spectrum in Fig. 32. The presence of 1 weight % of Cu promoter does not appreciably increase the extent of iron reduction (Fig. 33), and, unlike the situation observed for precipitated catalysts, even the copper is not fully reduced by treatment in H₂ at 300 °C (Fig. 34). The spectrum in Fig. 35 indicates that treatment of the silica gel-supported catalyst in 1 atm of a 2:1 mixture of H₂/CO is also ineffective in promoting reduction of surface iron to the zero-valent state.

The reduction behaviors of the impregnated catalysts appear to be somewhat more complex than those of the precipitated materials, as shown by the TPR profile in Fig. 36. The peaks

observed at $< 600^{\circ}\text{C}$ are caused by successive partial reduction of various $\text{FeO}_x\text{-SiO}_2$ phases that are generated during the heating process, while those at $> 600^{\circ}\text{C}$ are due to final reduction of these phases to metallic iron. Figs. 37-39 demonstrate that, as observed for the precipitated catalysts, increasing levels of copper promoter increase the rate of the first step of iron reduction ($\text{Fe}_2\text{O}_3 \rightarrow \text{Fe}_3\text{O}_4$), but have a less well-defined influence on the second step ($\text{Fe}_3\text{O}_4 \rightarrow \text{Fe}$) of the reduction process. It should be noted that the TPR profile shown in Fig. 39 for the 25 weight % Fe/SiO₂ catalyst containing 3 weight % Cu closely resembles that of the 100 Fe/5 Cu/8 SiO₂ precipitated catalyst (curve (a)) in Fig. 9). A TPR profile obtained for an unpromoted 25 weight % Fe/SiO₂ that had previously been treated in H₂ for 16 h at 300 °C (Fig. 40) lacks the low temperature peaks observed in Fig. 36, but again indicates that complete reduction to zero-valent Fe⁰ does not occur during such treatment. The presence of 1 weight % of Cu promoter does not significantly alter the reduction behavior (Fig. 41). The TPR profile in Fig. 42 confirms that treatment in H₂ at 500 °C, although more effective than that at 300 °C, is still unable to completely reduce the supported iron.

FT-IR studies of NO adsorption on certain of the precipitated and silica gel-supported iron catalysts have also been made. Infrared spectra obtained previously for NO adsorption on the unpromoted 25 weight % Fe/SiO₂ material have shown that, following treatment in O₂ at 300 °C and subsequent evacuation at 300 °C prior to cooling in vacuum to room temperature, exposure to gaseous NO resulted in formation of a single, intense infrared band at $\sim 1810\text{ cm}^{-1}$. The latter was ascribed to the N-O stretching vibration of NO adsorbed on oxidized iron sites. If, following calcination and evacuation, the sample was treated in H₂ at 300 °C prior to exposure to NO, a second band appeared at $\sim 1760\text{ cm}^{-1}$, in addition to the 1810 cm^{-1} band. The former was ascribed to NO adsorption on partially reduced iron sites.

We have recently obtained spectra for NO adsorption on a sample of the unpromoted, precipitated iron catalyst by depositing a thin film of the material onto a CaF₂ single crystal from an acetone slurry. Following calcination in O₂ at 300 °C and subsequent evacuation at the same temperature, the unreduced sample was exposed to gaseous NO at 25 °C to produce the infrared spectrum shown in Fig. 43. This spectrum closely resembles that obtained previously for the 25

weight % Fe/SiO₂ material *after* it had been treated in H₂ at 300 °C. These results again indicate the much greater ease with which the unsupported, precipitated iron catalysts are reduced compared to their silica-supported counterparts, but also demonstrate that treatment in H₂ at 300 °C is ineffective in causing reduction of *surface* iron to the metallic state, even for the unsupported catalysts. Exposure of the unpromoted iron precipitate to 1 atm of a 2/1 mixture of H₂/CO at 300 °C leads to more extensive reduction, as shown by the spectrum of adsorbed NO in Fig. 44, a behavior also exhibited by the silica gel-supported catalyst, although the resulting bands in the former case occur at lower frequencies (1777 and 1706 cm⁻¹) than the corresponding bands observed for the latter (1800 and 1740 cm⁻¹). The band occurring at 1706 cm⁻¹ on the precipitated catalyst is likely due to NO adsorbed on zero-valent iron, the only spectroscopic evidence observed thus far for metallic *surface* iron species. This result is consistent with previously reported observations that, although H₂ treatment of the copper-free precipitated catalysts at 300 °C does not lead to complete reduction, similar treatment in either CO or H₂/CO does effect reduction to metallic iron.

TASK 3 — Process Evaluation Research

The most promising catalysts prepared and tested during the current investigation will be subjected to a more thorough process evaluation in slurry reactors. These catalysts will also be compared to state of the art catalysts (*e.g.*, Ruhrchemie LP 33/81) tested under similar process conditions. Stability studies will be conducted in slurry reactors with the process conditions held at fixed values for long durations. These tests will show the effects of catalyst aging on catalyst activity and selectivity as well as the extent of catalyst deactivation.

A slurry reactor test of Ruhrchemie LP 33/81 catalyst has been initiated (run SA-99-0888). The catalyst (< 325 *mesh*) was loaded in the reactor with an excess of purified *n*-octacosane, and reduced *in situ* at 280 °C, 16 h with CO reductant. Following reduction, the excess wax was withdrawn from the reactor to give a static slurry volume of 385 cc. The reactor was brought to a fixed set of conditions after reduction, 250 °C, 1.48 MPa, 2 Nl g-cat·h, (H₂/CO) = 0.67 (nominal), which were held constant to evaluate the stability of the catalyst. Catalyst activity increased during the first part of the run, and stabilized at about 45 % (H₂+CO) conversion after

18 h on stream. During the next 60 h, the (H_2+CO) conversions were constant, varying between 43.8 and 47.6 %. Run SA-99-0888 is still in progress, and the results will be discussed in detail in future reports.

Task 4 - Economic Evaluation

No work on this task was scheduled during this quarter.

V. LITERATURE REFERENCES

- Bukur, D. B., R. F. Brown, "Fischer-Tropsch Synthesis in a Stirred Tank Slurry Reactor — Reaction Rates," *Can. J. Chem. Eng.*, **65**, 604-612 (1987).
- Dry, M. E., in "Catalysis — Science and Technology," Vol. I, Anderson, J. R. and M. Boudart, Eds., Springer-Verlag, New York (1981) p. 159.
- Feimer, J. L., P. L. Silveston, R. R. Hudgins, "Steady-State Study of the Fischer-Tropsch Reaction," *Ind. Eng. Chem. Prod. Res. Dev.*, **20**, 609-615 (1981).
- Huff, G. A., Jr., and C. N. Satterfield, "Intrinsic Kinetics of the Fischer-Tropsch Synthesis on a Reduced Fused-Magnetite Catalyst," *Ind. Eng. Chem. Process Des. Dev.*, **23**, 696-705 (1984).
- Kuo, J. C. W., *et al*, "Slurry Fischer-Tropsch/Mobil Two-Stage Process of Converting Syngas to High Octane Gasoline," Final Report to U.S. Dept. of Energy, Contract No. DE-AC22-83PC60019 (1985).
- Nettelhoff, H., R. Kokuun, S. Ledakowicz, and W.-D. Deckwer, "Studies on the Kinetics of Fischer-Tropsch Synthesis in Slurry Phase," *Ger. Chem. Eng.*, **8**, 177-185 (1985).
- Newsome, D. S., "The Water-Gas Shift Reaction," *Catal. Rev.—Sci. Eng.*, **21**, 275-318 (1980).
- Satterfield, C. N., and G. A. Huff, Jr., "Mass Transfer and Product Selectivity in a Mechanically Stirred Fischer-Tropsch Slurry Reactor," *A.C.S. Symposium Series*, **196**, 225-236 (1982).

Table 1. Conditions selected for wax analysis procedure.

Instrument: Varian 3400 (capillary)
Sample: $1.5\mu\text{l}$, 12 mg/ml CS_2
Column: RSL-150, $0.53\text{-mm ID}\times 15\text{-m}$
Column Program: $35\text{ }^\circ\text{C}$, hold 2 min
 $35 - 320\text{ }^\circ\text{C}$ @ $4\text{ }^\circ/\text{min}$
 $320\text{ }^\circ\text{C}$, hold 10 min
Detector: FID, $400\text{ }^\circ\text{C}$
Injector: Programmable On-column
Injector Program: $35\text{ }^\circ\text{C}$, hold 2 min
 $35 - 320\text{ }^\circ\text{C}$ @ $100\text{ }^\circ/\text{min}$
 $320\text{ }^\circ\text{C}$, hold 78.4 min
Carrier: He, 2 ml/min
Makeup: He, 25 ml/min

Table 2. Response factors and percent relative deviations for wax analysis standard. Varian 3400 GC, RSL-150 column.

Component	Weight %	Response				Factor	
		Injection			#	Average	% Dev
		1	2	3			
<i>n</i> -Hexadecane (C ₁₆) ¹	8.46	1.00	1.00	1.00	1.00	1.00	—
<i>n</i> -Octadecane (C ₁₈)	8.73	0.983	0.991	0.996	1.01	0.994	1.0
<i>n</i> -Eicosane (C ₂₀)	7.73	0.714	0.764	0.777	0.787	0.761	4.2
1-Eicosene (C ₂₀)	7.89	0.973	0.929	0.920	0.929	0.938	2.6
<i>n</i> -Docosane (C ₂₂)	8.98	1.00	1.00	1.00	1.01	1.00	0.4
<i>n</i> -Tetracosane (C ₂₄)	8.67	0.982	0.977	0.978	0.988	0.981	0.5
<i>n</i> -Hexacosane (C ₂₆)	8.34	0.981	0.976	0.978	0.990	0.982	0.6
<i>n</i> -Octacosane (C ₂₈)	8.06	0.975	0.970	0.973	0.986	0.976	0.7
<i>n</i> -Triacontane (C ₃₀)	8.56	0.961	0.958	0.962	0.977	0.965	0.8
<i>n</i> -Hexatriacontane (C ₃₆)	8.15	0.938	0.933	0.934	0.956	0.940	1.1
<i>n</i> -Tetracontane (C ₄₀)	8.37	0.928	0.924	0.924	0.948	0.931	1.2
<i>n</i> -Tetratetracontane (C ₄₄)	8.06	0.956	0.966	0.928	0.950	0.950	1.7

¹ Reference component

Table 3. Wax analysis results for run FA-63-0418-5. Average weight percent of two injections, percent relative deviations are shown in parentheses.

Carbon #	Weight % of Sample		
	n-Paraffin	(1+2)-Olefins	Isomers†
8			0.023 (17.1)
9			0.035 (5.95)
10	0.035 (33.6)	0.085 (8.57)	0.046 (2.90)
11	0.045 (6.70)	0.109 (4.26)	0.082 (2.56)
12	0.072 (4.95)	0.162 (2.11)	0.100 (0.67)
13	0.097 (0.28)	0.230 (0.91)	0.147 (10.2)
14	0.134 (0.17)	0.313 (0.94)	0.202 (3.11)
15	0.182 (0.21)	0.403 (0.53)	0.249 (5.02)
16	0.255 (0.43)	0.572 (0.63)	0.359 (2.17)
17	0.357 (0.65)	0.644 (2.64)	0.370 (1.36)
18	0.481 (0.57)	0.778 (4.26)	0.483 (8.76)
19	0.612 (0.02)	0.877 (0.47)	0.570 (1.48)
20	0.747 (0.19)	0.928 (0.47)	0.627 (1.86)
21	0.856 (0.21)	0.993 (1.19)	0.621 (10.3)
22	0.949 (1.07)	0.991 (0.69)	0.643 (1.06)
23	0.987 (0.98)	1.02 (1.10)	0.612 (3.91)
24	1.02 (0.88)	0.729 (1.25)	0.608 (1.39)
25	1.02 (1.57)	0.679 (0.35)	0.737 (2.63)
26	1.04 (1.57)	0.617 (0.12)	0.726 (4.95)
27	1.05 (0.11)	0.546 (2.56)	0.733 (5.60)
28	1.55 (0.69)		0.855 (3.60)
29	1.49 (0.33)		0.842 (12.9)
30	1.46 (0.60)		0.677 (5.45)
31	1.41 (1.19)		0.864 (33.8)
32	1.40 (2.26)		0.833 (28.3)
33	1.47 (11.1)		0.833 (14.2)
34	1.48 (2.35)		0.790 (1.75)
35	1.44 (3.06)		0.719 (20.7)
36	1.41 (2.92)		0.668 (0.84)
37	1.35 (3.20)		0.653 (13.5)
38	1.32 (3.97)		0.673 (5.15)
39	1.30 (5.60)		0.702 (16.3)
40	1.32 (4.30)		0.751 (3.42)
41	1.29 (2.95)		0.619 (51.7)
42	1.29 (4.44)		0.95 (12.3)
43	1.27 (5.89)		0.90 (20.8)
44	1.30 (6.37)		0.82 (62.3)
45	1.28 (1.75)		1.09 (22.4)
46	1.32 (1.91)		1.11 (34.2)
47	1.43 (1.14)		1.24 (13.9)
48	1.45 (2.15)		1.41 (8.58)
49	1.83 (18.3)		1.10 (46.8)
C ₅ -C ₁₁	0.080 (18.6)	0.194 (6.14)	0.187 (3.63)
C ₁₂ +	40.7 (3.17)	10.5 (0.08)	26.9 (2.67)
C ₉ -C ₂₅	7.85 (0.73)	9.51 (0.06)	6.49 (1.11)
C ₂₆ +	32.9 (3.79)	1.16 (1.27)	20.5 (3.86)
Total	40.8 (3.20)	10.7 (0.19)	27.1 (2.68)

† Includes oxygenates

Table 4. Comparison of lumped hydrocarbon product distributions with and without wax analysis.

Fraction	Weight % of Hydrocarbons	
	Analyzed Wax	Unanalyzed Wax
CH ₄	2.93	2.84
C ₂ -C ₄	18.1	17.5
C ₅ -C ₁₁	17.4	16.7
C ₁₂ +, excluding unanalyzed wax	48.2	2.73
C ₁₂ +, including unanalyzed wax	61.6	63.0
Unanalyzed Wax	13.4 ¹	60.2 ²

¹ Calculated from the weight recovery of the wax analysis.

² Unanalyzed products collected in hot trap.

Table 5. Summary of results for fixed bed run FA-63-0418.

Catalyst: 3.60 g^a, 100 Fe/5 Cu /4.2 K/8 SiO₂
 Catalyst volume: 3.80 cc
 Diluent: 35.0 g, Glass beads
 Diluent Volume: 23.0 cc

Period	1	2	3	4	5	6
Date	2/12/88	2/13/88	2/14/88	2/15/88	2/16/88	2/17/88
Time on Stream (h)	49.0	72.0	96.0	121.0	145.0	169.0
Balance Duration (h)	6.0	6.0	6.0	6.0	6.0	6.0
Average Temperature (°C)	235.	235.	250.	220.	235.	235.
Maximum Δ Temperature (°C) ^b	7.60	7.60	10.1	4.30	8.50	.800
Pressure (MPa)	1.48	1.48	1.48	1.48	3.00	1.48
H ₂ /CO Feed Ratio	1.10	1.10	1.10	1.10	1.10	1.10
Space Velocity (NI/g-cat·h) ^a	2.00	4.01	4.01	2.00	4.01	2.00
Space Velocity (NI/g-Fe·h)	3.34	6.67	6.67	3.33	6.67	3.34
GHSV (h ⁻¹) ^c	267	534	534	267	534	267
CO Conversion (%)	93.8	64.5	80.5	73.6	46.4	52.9
H ₂ +CO Conversion (%)	76.7	52.8	65.1	62.1	42.7	44.8
H ₂ /CO Usage	.713	.715	.698	.773	.933	.782
STY (mols H ₂ +CO/g-cat·h) ^a	.069	.094	.116	.055	.076	.040
$P_{CO_2} \cdot P_{H_2} / P_{CO} \cdot P_{H_2O}$	28.4	6.13	13.8	7.52	2.42	3.89
Weight % of Outlet						
H ₂	2.89	4.37	3.70	3.70	4.50	4.64
H ₂ O	6.06	4.88	4.36	5.19	5.35	5.06
CO	5.82	33.9	18.6	25.5	50.2	44.2
CO ₂	61.1	40.8	53.1	47.4	25.5	33.0
Hydrocarbons	11.1	6.97	6.55	6.26	5.51	4.99
Oxygenates	1.44	.902	.787	.840	.542	.734
Wax ^d	11.6	8.08	12.9	11.2	8.35	7.41
Yield (g/Nm ³ H ₂ + CO Converted)						
CH ₄	6.53	5.81	6.85	4.78	5.85	6.07
C ₂ -C ₄ Hydrocarbons	30.9	30.0	29.8	27.7	36.1	32.9
C ₅ -C ₁₁ Hydrocarbons	37.8	36.0	23.0	26.5	34.3	29.0
C ₁₂ + Hydrocarbons	113.	106.	126.	114.	130.	107.
Wax ^d	96.0	95.4	123.	111.	124.	105.
Oxygenates	11.9	10.6	7.52	8.32	8.06	10.4
Total	200.	188.	193.	181.	214.	186.
1+2 Olefins/n-Paraffin Ratio						
C ₂	2.39	2.20	2.68	2.41	2.16	1.91
C ₃	6.18	6.09	6.73	5.72	4.79	6.06
C ₄	4.96	4.90	5.40	4.61	3.94	4.90
C ₈	3.87	3.66	4.15	3.63	3.55	3.80
C ₁₀	3.44	2.86	3.64	3.15	2.95	3.35

^a Based on unreduced catalyst^b Maximum axial temperature difference^c Based on reactor volume^d Unanalyzed products collected from hot trap

Table 5 (cont'd). Summary of results for fixed bed run FA-63-0418.

Period		1	2	3	4	5	6
Weight % of Hydrocarbons							
C ₁₁ H ₄		3.47	3.27	3.69	2.77	2.84	3.46
Ethane		1.67	1.99	1.58	1.68	1.95	2.51
Ethylene		3.72	4.07	3.96	3.79	3.92	4.47
Propane		.867	.852	.763	.879	1.11	.937
Propylene		5.11	4.95	4.90	4.79	5.05	5.42
n-Butane		.803	.806	.714	.817	1.04	.864
1+2 Butenes		3.85	3.81	3.72	3.64	3.95	4.09
C ₄ Isomers		.419	.432	.383	.431	.521	.474
n-Pentane		1.05	1.13	1.01	1.11	1.34	1.18
1+2 Pentenes		3.26	3.48	3.31	3.27	3.57	3.53
C ₅ Isomers		.234	.265	.224	.252	.330	.277
n-Hexane		.573	.692	.478	.633	.758	.620
1+2 Hexenes		2.24	2.75	2.08	2.40	2.77	2.49
C ₆ Isomers		.414	.534	.386	.456	.531	.595
n-Heptane		.483	.503	.317	.414	.519	.407
1+2 Heptenes		1.86	1.92	1.33	1.56	1.84	1.54
C ₇ Isomers		.316	.368	.315	.309	.572	.748
n-Octane		.479	.434	.138	.275	.267	.201
1+2 Octenes		1.82	1.56	.563	.983	.929	.749
C ₈ Isomers		.211	.278	.0491	.113	.0602	.0649
n-Nonane		.493	.410	.150	.279	.202	.267
1+2 Nonenes		1.77	1.30	.540	.879	.656	.871
C ₉ Isomers		.195	.183	.0620	.109	.0794	.0829
n-Decane		.515	.519	.157	.291	.258	.334
1+2 Decenes		1.75	1.47	.564	.903	.750	1.10
C ₁₀ Isomers		.217	.298	.0720	.148	.130	.144
n-Undecane		.487	.505	.134	.223	.252	.284
1+2 Undecenes		1.57	1.31	.473	.666	.665	.914
C ₁₁ Isomers		.185	.338	.0583	.109	.175	.138
C ₂ -C ₄		16.4	16.9	16.0	16.0	17.5	18.8
C ₅ -C ₁₁		20.1	20.2	12.4	15.4	16.7	16.5
C ₁₂ +		60.0	59.6	67.9	65.8	63.0	61.3
Wax ^d		51.0	53.7	66.3	64.0	60.2	59.8

^d Unanalyzed wax collected from hot trap

Table 6. Summary of results for fixed bed run FA-66-0548.

Catalyst: 2.71 g^a, 100 Fe/5 Cu/4.2 K/25 SiO₂
Catalyst volume: 3.60 cc

Diluent: 34.9 g, Glass beads
Diluent Volume: 23.0 cc

Period	1	2	3	4	5
Date	2/25/88	2/26/88	2/27/88	2/28/88	2/29/88
Time on Stream (h)	40.0	72.5	95.5	120.0	144.5
Balance Duration (h)	6.5	6.0	7.0	7.0	6.0
Average Temperature (°C)	234.	235.	250.	220.	235.
Maximum Δ Temperature (°C) ^b	4.20	4.20	3.80	2.80	5.30
Pressure (MPa)	1.48	1.48	1.48	1.48	2.96
H ₂ /CO Feed Ratio	1.00	1.00	1.00	1.00	1.00
Space Velocity (Nl/g-cat-h) ^a	2.00	4.01	2.01	2.01	4.01
Space Velocity (Nl/g-Fe-h)	4.01	8.01	4.03	4.03	8.01
GHSV (h ⁻¹) ^c	201	402	202	202	402
CO Conversion (%)	59.6	39.4	78.2	29.7	49.5
H ₂ +CO Conversion (%)	55.0	38.5	67.6	31.1	48.1
H ₂ /CO Usage	.845	.955	.730	1.09	.942
STY (mols H ₂ +CO/g-cat-h) ^a	.049	.069	.061	.028	.086
$P_{CO_2} \cdot P_{H_2} / P_{CO} \cdot P_{H_2O}$	2.82	1.32	7.33	.863	2.04
Weight % of Outlet					
H ₂	3.45	4.25	3.00	4.49	3.70
H ₂ O	6.28	6.26	5.65	6.35	5.61
CO	39.0	57.3	21.1	64.9	48.7
CO ₂	35.2	19.7	51.4	13.9	26.4
Hydrocarbons	6.87	5.53	10.8	4.95	6.39
Oxygenates	.728	.741	.844	.720	.792
Wax ^d	8.47	6.17	7.23	4.65	8.38
Yield (g/Nm ³ H ₂ + CO Converted)					
CH ₄	10.2	10.1	13.8	10.2	8.08
C ₂ -C ₄ Hydrocarbons	41.1	44.9	51.4	48.3	45.2
C ₅ -C ₁₁ Hydrocarbons	27.5	35.5	34.0	43.2	30.7
C ₁₂ + Hydrocarbons	102.	110.	72.0	107.	115.
Wax ^d	99.8	106.	68.9	101.	113.
Oxygenates	8.58	12.7	8.04	15.6	10.7
Total	189.	213.	179.	224.	209.
1+2 Olefins/n-Paraffin Ratio					
C ₂	1.90	1.51	1.24	2.70	1.60
C ₃	6.48	6.35	6.98	5.70	4.71
C ₄	5.20	5.14	5.49	4.54	3.85
C ₅	4.06	3.62	3.42	2.48	3.26
C ₁₀	3.37	3.25	3.01	3.07	3.06

^a Based on unreduced catalyst

^c Based on reactor volume

^b Maximum axial temperature difference

^d Unanalyzed products collected from hot trap

Table 6 (cont'd). Summary of results for fixed bed run FA-66-0548.

Period		1	2	3	4	5
Weight % of Hydrocarbons						
CH ₄		5.64	5.03	8.07	4.88	4.07
Ethane		2.53	3.44	4.45	2.06	2.97
Ethylene		4.47	4.83	5.15	5.20	4.44
Propane		1.18	1.06	1.48	1.31	1.46
Propylene		7.31	6.45	9.83	7.12	6.55
n-Butane		1.12	1.03	1.34	1.28	1.42
1+2 Butenes		5.60	5.10	7.12	5.61	5.27
C ₄ Isomers		.537	.487	.654	.554	.641
n-Pentane		1.40	1.30	1.67	1.57	1.75
1+2 Pentenes		4.81	4.46	5.88	4.92	4.73
C ₅ Isomers		.306	.283	.391	.332	.404
n-Hexane		.695	.826	.702	1.43	.687
1+2 Hexenes		2.27	3.24	2.12	3.10	2.22
C ₆ Isomers		.436	.594	.443	.845	.419
n-Heptane		.307	.497	.358	.762	.280
1+2 Heptenes		1.15	1.87	1.31	1.57	1.12
C ₇ Isomers		.355	.397	.220	.326	.422
n-Octane		.150	.281	.383	.468	.171
1+2 Octenes		.597	.998	1.28	1.14	.547
C ₈ Isomers		.0720	.221	.0974	.118	.0367
n-Nonane		.205	.178	.471	.279	.240
1+2 Nonenes		.701	.567	1.42	.822	.654
C ₉ Isomers		.0792	.0746	.245	.116	.0827
n-Decane		.211	.214	.388	.345	.225
1+2 Decenes		.700	.685	1.15	1.04	.679
C ₁₀ Isomers		.100	.121	.226	.201	.0930
n-Undecane		.145	.197	.254	.301	.145
1+2 Undecenes		.472	.602	.724	.838	.476
C ₁₁ Isomers		.0735	.115	.139	.181	.0672
C ₂ -C ₄		22.7	22.4	30.0	23.1	22.7
C ₅ -C ₁₁		15.2	17.7	19.9	20.7	15.5
C ₁₂ +		56.4	54.9	42.0	51.3	57.7
Wax ^d		55.2	52.7	40.2	48.4	56.7

^d Unanalyzed wax collected from hot trap

Table 7. Summary of results for fixed bed run FA-69-0668.

Catalyst: 3.40 g^a, 100 Fe/5 Cu/4.2 K/100SiO₂
 Catalyst volume: 7.40 cc

Diluent: 30.8 g, Glass beads
 Diluent Volume: 20.0 cc

Period	1	2	3	4	5	6
Date	3/09/88	3/10/88	3/11/88	3/12/88	3/13/88	3/14/88
Time on Stream (h)	40.5	72.0	96.0	119.0	143.0	169.0
Balance Duration (h)	7.0	6.0	6.5	8.0	7.0	6.0
Average Temperature (°C)	234.	235.	250.	220.	235.	235.
Maximum Δ Temperature (°C) ^b	3.20	3.90	3.30	3.00	2.80	2.70
Pressure (MPa)	1.48	1.48	1.48	1.48	1.48	2.96
H ₂ /CO Feed Ratio	1.00	1.00	1.00	1.00	1.00	1.00
Space Velocity (NI/g-cat·h) ^a	1.99	3.99	1.99	2.01	1.99	3.99
Space Velocity (NI/g-Fe·h)	5.07	10.1	5.07	5.12	5.07	10.1
GHSV (h ⁻¹) ^c	247.	493.	247.	249.	247.	493.
CO Conversion (%)	24.3	17.5	30.8	11.3	20.1	22.4
H ₂ +CO Conversion (%)	29.1	22.0	35.2	15.8	25.7	29.4
H ₂ /CO Usage	1.39	1.51	1.29	1.79	1.56	1.63
STY (mols H ₂ +CO/g-cat·h) ^a	.026	.039	.031	.014	.023	.052
P _{CO₂} · P _{H₂} / P _{CO} · P _{H₂O}	.274	.172	.508	.125	.214	.141
Weight % of Outlet						
H ₂	4.57	5.00	4.15	5.35	4.64	4.39
H ₂ O	8.06	6.89	8.04	5.37	7.97	8.68
CO	72.6	77.9	66.2	82.8	75.0	74.4
CO ₂	6.17	3.26	11.5	1.82	4.86	3.66
Hydrocarbons	3.66	2.39	5.23	1.96	3.07	3.08
Oxygenates	.777	.612	.675	.379	.753	.797
Wax ^d	4.15	3.91	4.22	2.35	3.71	4.94
Yield (g/Nm ³ H ₂ + CO Converted)						
CH ₄	9.08	8.41	10.3	8.33	9.10	8.02
C ₂ -C ₄ Hydrocarbons	30.1	28.1	32.5	28.8	29.6	27.8
C ₆ -C ₁₁ Hydrocarbons	35.6	31.2	45.3	33.2	32.5	27.5
C ₁₂ + Hydrocarbons	100.	122.	87.1	112.	105.	115.
Wax ^d	93.0	117.	78.3	99.2	96.2	110.
Oxygenates	17.4	18.4	12.5	16.0	19.5	17.7
Total	192.	208.	188.	198.	195.	196.
1+2 Olefins/n-Paraffin Ratio						
C ₂	1.95	2.19	1.71	2.60	2.29	2.44
C ₃	6.14	6.31	6.89	5.59	6.29	4.54
C ₄	4.80	4.85	5.32	4.12	4.84	3.51
C ₆	2.87	2.72	3.21	2.85	2.83	2.56
C ₁₀	2.16	2.43	2.14	2.34	2.25	2.07

^a Based on unreduced catalyst

^c Based on reactor volume

^b Maximum axial temperature difference

^d Unanalyzed products collected from hot trap

Table 7 (cont'd). Summary of results for fixed bed run FA-69-0668.

Weight % of Hydrocarbons	Period					
	1	2	3	4	5	6
CH ₄	5.19	4.44	5.90	4.58	5.17	4.51
Ethane	1.86	1.71	2.21	1.64	1.59	1.26
Ethylene	3.39	3.49	3.53	3.96	3.39	2.86
Propane	.885	.697	.852	.823	.857	1.10
Propylene	5.18	4.19	5.60	4.39	5.14	4.76
n-Butane	.982	.788	.977	.954	.968	1.20
1+2 Butenes	4.56	3.69	5.02	3.79	4.53	4.06
C ₄ Isomers	.376	.292	.377	.292	.355	.357
n-Pentane	1.22	.997	1.30	1.09	1.23	1.36
1+2 Pentenes	4.48	4.31	5.77	3.92	4.38	3.88
C ₅ Isomers	.294	.399	.532	.191	.227	.244
n-Hexane	1.10	1.05	1.15	1.07	.895	.865
1+2 Hexenes	3.09	3.15	3.48	3.31	2.97	2.53
C ₆ Isomers	.386	.462	.549	.400	.407	.358
n-Heptane	.712	.731	.765	.805	.618	.589
1+2 Heptenes	2.21	2.11	2.28	2.40	1.85	1.56
C ₇ Isomers	.276	.263	.404	.217	.221	.292
n-Octane	.473	.400	.508	.468	.356	.338
1+2 Octenes	1.33	1.07	1.60	1.31	.990	.849
C ₈ Isomers	.0455	.0386	.0319	.130	.0395	.0416
n-Nonane	.377	.0867	.632	.168	.310	.202
1+2 Nonenes	.866	.236	1.57	.430	.745	.436
C ₉ Isomers	.0348	.00710	.0581	.0142	.0290	.0236
n-Decane	.550	.160	.878	.326	.488	.302
1+2 Decenes	1.17	.384	1.86	.753	1.08	.614
C ₁₀ Isomers	.0645	.0165	.0941	.0239	.0571	.0405
n-Undecane	.575	.187	.841	.387	.526	.319
1+2 Undecenes	1.05	.396	1.45	.805	1.02	.593
C ₁₁ Isomers	.0739	.0211	.0975	.0353	.0638	.0436
C ₂ -C ₄	17.2	14.9	18.6	15.8	16.8	15.6
C ₅ -C ₁₁	20.4	16.5	25.8	18.3	18.5	15.5
C ₁₂ +	57.2	64.2	49.7	61.4	59.5	64.4
Wax ^d	53.2	62.1	44.7	54.5	54.7	61.6

^d Unanalyzed wax collected from hot trap

Table 8. Activity and selectivity comparison of the SiO₂ supported catalysts, Ruhrchemie LP 33/81, and 100 Fe/3 Cu/0.2 K catalyst.

Nominal Conditions	Catalyst ¹	% Conversion		(H ₂ /CO) Usage	STY ²	Weight % of Hydrocarbons				
		(H ₂ +CO)	CO			CH ₄	C ₂ -C ₄	C ₅ -C ₁₁	C ₁₂ +	
220 °C, 1.48 MPa 2 NI/g-cat.h	63 (4)	62.1	73.6	.77	.055	2.77	16.0	15.4	65.8	
	66 (4)	31.1	29.7	1.09	.028	4.88	23.1	20.7	51.3	
	69 (4)	15.8	11.3	1.79	.014	4.58	15.8	18.3	61.4	
	99 (1)	37.9	37.8	1.10	.034	4.93	20.8	19.1	55.3	
	25 (1)	42.9	41.2	1.16	.039	4.31	19.9	20.2	29.6	
235 °C, 1.48 MPa 2 NI/g-cat.h	63 (1)	76.7	93.8	.71	.069	3.47	16.4	20.1	60.0	
	66 (1)	55.0	59.6	.85	.049	5.64	22.7	15.2	56.4	
	69 (1)	29.1	24.3	1.39	.026	5.19	17.2	20.4	57.2	
	99 (2)	43.7	39.6	1.31	.039	7.98	36.4	26.3	29.4	
	25 (2)	54.4	54.5	1.07	.05	7.80	37.3	29.6	25.3	
235 °C, 1.48 MPa 4 NI/g-cat.h	63 (2)	52.8	64.5	.72	.094	3.27	16.9	20.2	59.6	
	66 (2)	38.5	39.4	.96	.069	5.03	22.4	17.7	54.9	
	69 (2)	22.0	17.5	1.51	.039	4.44	14.9	16.5	64.2	
	99 (3)	33.7	28.6	1.47	.060	8.24	37.5	27.9	26.4	
	25 (3)	26.0	25.6	1.10	.047	6.00	26.9	28.8	38.3	
250 °C, 1.48 MPa 2 NI/g-cat.h	63 (3) ³	65.1	80.5	.70	.116	3.69	16.0	12.4	67.9	
	66 (3)	67.6	78.2	.73	.061	8.07	30.0	19.9	42.0	
	69 (3)	30.8	35.2	1.29	.031	5.90	18.6	25.8	49.7	
	99 (4)	60.6	64.4	.97	.054	7.60	32.0	28.1	32.4	
	25 (4)	72.2	81.7	.83	.066	10.3	36.8	32.8	20.0	

¹ FA-63-0418 (100 Fe/5 Cu/4.2 K/8 SiO₂)
 FA-66-0548 (100 Fe/5 Cu/4.2 K/25 SiO₂)
 FA-69-0668 (100 Fe/5 Cu/4.2 K/100 SiO₂)
 FB-99-3477 (Ruhrchemie LP 33/81)
 FA-25-2447 (100 Fe/3 Cu/0.2 K)
 Balance number shown in parentheses

² STY in mols (H₂+CO) Converted/g-cat.h

³ SV = 4.0 NI/g-cat.h

Table 9. Summary of results for fixed bed run FA-73-0828.

Catalyst: 3.40 g^a, 100 Fe/5 Cu/4.2 K/8 Al₂O₃
 Catalyst volume: 3.00 cc
 Diluent: 36.6 g, Glass beads
 Diluent Volume: 24.0 cc

Period	1	2	3	4	5	6
Date	3/24/88	3/25/88	3/26/88	3/27/88	3/28/88	3/29/88
Time on Stream (h)	41.0	72.0	96.0	118.5	143.5	168.0
Balance Duration (h)	6.5	6.0	6.0	7.5	6.5	5.5
Average Temperature (°C)	235.	234.	250.	220.	235.	235.
Maximum Δ Temperature (°C) ^b	7.20	3.70	7.50	2.00	2.60	2.20
Pressure (MPa)	1.48	1.48	1.48	1.48	1.48	2.96
H ₂ /CO Feed Ratio	1.00	1.00	1.00	1.00	1.00	1.00
Space Velocity (Nl/g-cat·h) ^a	2.01	4.02	4.02	2.01	2.01	4.01
Space Velocity (Nl/g-Fe·h)	3.27	6.53	6.53	3.27	3.27	6.50
GHSV (h ⁻¹) ^c	253.	507.	507.	253.	253.	504.
CO Conversion (%)	90.3	56.0	69.8	36.9	50.8	42.2
H ₂ +CO Conversion (%)	75.1	47.0	57.8	31.7	42.9	40.0
H ₂ /CO Usage	.664	.679	.657	.717	.686	.896
STY (mols H ₂ +CO/g-cat·h) ^a	.067	.084	.104	.028	.038	.071
P _{CO₂} · P _{H₂} / P _{CO} · P _{H₂O}	23.9	6.61	9.91	2.90	4.37	1.88
Weight % of Outlet						
H ₂	2.75	4.18	3.75	5.12	4.46	4.27
H ₂ O	4.33	3.27	3.48	3.59	4.01	5.59
CO	9.26	41.2	29.0	61.0	46.8	55.1
CO ₂	61.5	37.5	47.0	21.9	32.4	23.9
Hydrocarbons	9.42	5.78	7.54	3.64	5.37	5.02
Oxygenates	1.22	.728	1.06	.579	.823	.711
Wax ^d	11.5	7.30	8.07	4.17	6.14	5.40
Yield (g/Nm ³ H ₂ + CO Converted)						
CH ₄	8.83	7.79	8.62	6.73	8.61	7.98
C ₂ -C ₄ Hydrocarbons	33.7	32.3	33.6	28.5	34.5	37.4
C ₅ -C ₁₁ Hydrocarbons	35.2	34.2	35.5	30.1	32.3	33.0
C ₁₂ + Hydrocarbons	105.	112.	97.8	94.1	101.	92.6
Wax ^d	101.	104.	90.8	85.0	94.0	88.6
Oxygenates	10.7	10.3	11.9	11.8	12.6	11.7
Total	193.	196.	187.	171.	189.	183.
1+2 Olefins/n-Paraffin Ratio						
C ₂	2.25	2.70	2.53	2.17	1.87	1.18
C ₃	5.67	6.35	7.46	5.49	6.31	4.88
C ₄	5.27	5.21	6.15	4.52	5.30	4.11
C ₈	3.68	3.75	3.88	3.21	3.90	2.87
C ₁₀	3.49	3.53	3.98	3.07	3.37	2.87

^a Based on unreduced catalyst^c Based on reactor volume^b Maximum axial temperature difference^d Unanalyzed products collected from hot trap

Table 9 (cont'd). Summary of results for fixed bed run FA-73-0828.

Period	1	2	3	4	5	6
Weight % of Hydrocarbons						
CH ₄	4.83	4.19	4.91	4.22	4.89	4.67
Ethane	1.79	1.63	1.77	2.05	2.28	3.53
Ethylene	3.75	4.11	4.18	4.15	3.98	3.88
Propane	1.10	.886	.872	1.01	1.02	1.36
Propylene	5.97	5.37	6.21	5.29	6.14	6.31
n-Butane	.874	.819	.809	.918	.924	1.25
1+2 Butenes	4.44	4.12	4.81	4.00	4.73	4.97
C ₄ Isomers	.486	.460	.513	.455	.514	.602
n-Pentane	1.17	1.16	1.23	1.21	1.28	1.58
1+2 Pentenes	3.77	4.14	4.31	4.10	4.25	4.56
C ₅ Isomers	.275	.382	.286	.448	.312	.431
n-Hexane	.622	.610	.583	.796	.571	.949
1+2 Hexenes	2.46	2.44	2.56	2.60	2.30	3.03
C ₆ Isomers	.527	.570	.590	.631	.550	.745
n-Heptane	.433	.401	.411	.542	.346	.603
1+2 Heptenes	1.70	1.60	1.73	1.68	1.40	1.82
C ₇ Isomers	.336	.391	.387	.499	.306	.520
n-Octane	.383	.325	.367	.310	.271	.352
1+2 Octenes	1.39	1.20	1.40	.976	1.04	.991
C ₈ Isomers	.226	.197	.247	.153	.0618	.149
n-Nonane	.406	.299	.352	.288	.350	.254
1+2 Nonenes	1.40	1.01	1.33	.844	1.16	.693
C ₉ Isomers	.330	.146	.277	.101	.139	.0695
n-Decane	.395	.353	.374	.414	.434	.315
1+2 Decenes	1.36	1.23	1.47	1.25	1.44	.891
C ₁₀ Isomers	.406	.227	.414	.193	.234	.112
n-Undecane	.324	.327	.337	.415	.405	.280
1+2 Undecenes	1.08	1.18	1.27	1.22	1.30	.828
C ₁₁ Isomers	.285	.229	.311	.219	.180	.106
C ₂ -C ₄	18.4	17.4	19.2	17.9	19.6	21.9
C ₅ -C ₁₁	19.3	18.4	20.2	18.9	18.3	19.3
C ₁₂ +	57.5	60.0	55.7	59.1	57.2	54.2
Wax ^d	55.0	55.8	51.7	53.3	53.4	51.8

^d Unanalyzed wax collected from hot trap

Table 10. Summary of results for fixed bed run FB-25-0098.

Catalyst: 2.75 g^a, 100 Fe/3 Cu/0.2 K
 Catalyst volume: 3.00 cc
 Diluent: 36.0 g, Glass beads
 Diluent Volume: 24.0 cc

Period	1	2
Date	1/12/88	1/14/88
Time on Stream (h)	70.8	118.8
Balance Duration (h)	8.0	8.0
Average Temperature (°C)	250.	250.
Maximum Δ Temperature (°C) ^b	2.00	2.00
Pressure (MPa)	1.48	1.48
H ₂ /CO Feed Ratio	1.10	1.10
Space Velocity (NI/g-cat·h) ^a	2.03	2.03
Space Velocity (NI/g-Fe·h)	2.98	2.98
GHSV (h ⁻¹) ^c	186.	186.
CO Conversion (%)	69.1	63.4
H ₂ +CO Conversion (%)	59.7	53.9
H ₂ /CO Usage	.811	.784
STY (mols H ₂ +CO/g-cat·h) ^a	.054	.049
$P_{CO_2} \cdot P_{H_2} / P_{CO} \cdot P_{H_2O}$	5.82	6.00
Weight % of Outlet		
H ₂	3.79	4.22
H ₂ O	5.08	4.46
CO	30.4	35.8
CO ₂	41.7	39.9
Hydrocarbons	14.8	12.3
Oxygenates	.649	.554
Wax ^d	3.65	2.76
Yield (g/Nm ³ H ₂ + CO Converted)		
CH ₄	14.0	14.2
C ₂ -C ₄ Hydrocarbons	53.1	53.6
C ₈ -C ₁₁ Hydrocarbons	69.1	60.9
C ₁₂ + Hydrocarbons	51.1	41.4
Wax ^d	37.1	31.2
Oxygenates	6.59	6.27
Total	194.	176.
1+2 Olefins/n-Paraffin Ratio		
C ₂	.626	.699
C ₃	4.17	4.45
C ₄	4.17	4.29
C ₈	1.96	1.99
C ₁₀	1.71	1.75

^a Based on unreduced catalyst^c Based on reactor volume^b Maximum axial temperature difference^d Unanalyzed products collected from hot trap

Table 10 (cont'd). Summary of results for fixed bed run FB-25-0098.

Period		1	2
Weight % of Hydrocarbons			
CH ₄		7.48	8.36
Ethane		5.12	5.54
Ethylene		2.99	3.61
Propane		2.10	2.20
Propylene		8.37	9.33
<i>n</i> -Butane		1.79	1.95
1+2 Butenes		7.20	8.06
C ₄ Isomers		.769	.835
<i>n</i> -Pentane		2.30	2.51
1+2 Pentenes		5.88	6.73
C ₅ Isomers		.934	.979
<i>n</i> -Hexane		1.50	1.93
1+2 Hexenes		3.23	3.98
C ₆ Isomers		.659	.819
<i>n</i> -Heptane		1.16	1.24
1+2 Heptenes		2.15	2.39
C ₇ Isomers		.413	.558
<i>n</i> -Octane		1.40	1.17
1+2 Octenes		2.70	2.30
C ₈ Isomers		.198	.340
<i>n</i> -Nonane		1.66	1.23
1+2 Nonenes		3.11	2.36
C ₉ Isomers		.505	.411
<i>n</i> -Decane		1.68	1.25
1+2 Decenes		2.83	2.16
C ₁₀ Isomers		.527	.452
<i>n</i> -Undecane		1.47	1.05
1+2 Undecenes		2.13	1.56
C ₁₁ Isomers		.435	.365
C ₂ -C ₄		28.3	31.5
C ₅ -C ₁₁		36.9	35.8
C ₁₂ +		27.3	24.3
Wax ^d		19.8	18.3

^d Unanalyzed wax collected from hot trap

Table 11. Nominal ranges of process variables studied in run SB-07-0458.

Temperature ($^{\circ}\text{C}$):	235, 250, 265
Pressure (MPa):	1.48, 2.96
Space Velocity ($\text{NI/g-cat}\cdot\text{h}$):	1.0, 2.0
Molar (H_2/CO) Feed Ratio:	0.67, 1.0

Table 12. Summary of results for slurry run SB-07-0458.

Catalyst: 29.8 g^a, 100 Fe/.3 Cu/0.5 K

Slurry liquid: 294 g, FT-300

Reactor volume: 375. cc^b

Period	1	2	3	4	5
Date	2/17/88	2/19/88	2/21/88	2/23/88	2/25/88
Time on Stream (h)	45.0	92.0	139.5	188.0	236.0
Balance Duration (h)	6.0	6.0	6.0	6.0	6.0
Average Temperature (°C)	250.	250.	265.	250.	250.
Pressure (MPa)	1.48	1.48	1.48	1.48	1.48
H ₂ /CO Feed Ratio	1.05	1.05	1.05	.711	.735
Space Velocity (Nl/g-cat·h) ^a	2.16	1.07	2.13	2.13	1.06
Space Velocity (Nl/g-Fe·h)	3.11	1.54	3.07	3.06	1.53
GHSV (h ⁻¹) ^b	172.	83.4	166.	165.	82.4
CO Conversion (%)	29.2	44.1	36.7	23.0	45.4
H ₂ +CO Conversion (%)	24.8	36.0	30.8	21.3	42.5
H ₂ /CO Usage	.742	.676	.717	.583	.623
STY (mols H ₂ +CO/g-cat·h) ^a	.024	.017	.029	.020	.020
P _{CO₂} · P _{H₂} /P _{CO} · P _{H₂O}	6.06	11.2	7.49	13.4	10.9
Weight % of Outlet					
H ₂	5.94	5.15	5.55	4.12	3.10
H ₂ O	1.26	1.32	1.44	.305	.971
CO	70.2	53.3	62.1	76.5	52.0
CO ₂	15.9	26.9	21.2	13.4	31.2
Hydrocarbons	4.22	8.57	7.24	3.76	7.04
Oxygenates	.252	.805	.610	.167	.555
Wax ^c	2.25	3.96	1.89	1.82	5.07
Yield (g/Nm ³ H ₂ + CO Converted)					
CH ₄	7.33	8.82	10.0	5.96	5.95
C ₂ -C ₄ Hydrocarbons	40.0	37.5	38.4	29.3	25.6
C ₅ -C ₁₁ Hydrocarbons	36.3	50.1	48.2	46.0	43.0
C ₁₂ + Hydrocarbons	76.4	126.	87.5	111.	141.
Wax ^c	55.7	70.4	38.1	62.8	90.1
Oxygenates	6.23	14.3	12.3	5.77	9.85
Total	166.	237.	196.	198.	225.
1+2 Olefins/n-Paraffin Ratio					
C ₂	1.20	1.56	1.39	.899	1.90
C ₃	4.06	4.52	5.27	4.92	5.13
C ₄	3.61	3.61	4.11	3.66	3.84
C ₈	3.03	2.60	2.67	3.29	2.80
C ₁₀	2.29	2.69	2.71	2.55	2.61

^a Based on unreduced catalyst^c Unanalyzed wax withdrawn from reactor^b Based on static slurry volume

Table 12 (cont'd). Summary of results for slurry run SB-07-0458.

Period	6	7	8	9	10
Date	2/27/88	2/29/88	3/02/88	3/04/88	3/05/88
Time on Stream (h)	284.0	284.0	380.0	428.0	452.0
Balance Duration (h)	6.0	6.0	6.0	6.0	6.0
Average Temperature (°C)	265.	265.	235.	250.	265.
Pressure (MPa)	1.48	1.48	1.48	1.48	2.96
H ₂ /CO Feed Ratio	.703	.721	.710	1.06	.727
Space Velocity (NI/g-cat.h) ^a	2.15	1.08	1.08	2.19	2.04
Space Velocity (NI/g-Fe.h)	3.10	1.56	1.56	3.15	2.94
GHSV (h ⁻¹) ^b	164.	80.8	79.1	157.	144.
CO Conversion (%)	55.6	75.9	31.0	44.4	79.2
H ₂ +CO Conversion (%)	51.2	70.8	29.2	35.5	73.0
H ₂ /CO Usage	.569	.606	.611	.648	.592
STY (mols H ₂ +CO/g-cat.h) ^a	.049	.034	.014	.035	.067
P _{CO₂} · P _{H₂} /P _{CO} · P _{H₂O}	25.7	39.7	10.8	13.5	25.3
Weight % of Outlet					
H ₂	2.78	1.72	3.52	5.38	1.79
H ₂ O	.543	.612	.616	1.23	1.12
CO	44.3	22.1	64.7	53.5	20.1
CO ₂	39.2	54.9	21.6	28.9	55.8
Hydrocarbons	7.12	10.5	5.05	6.58	10.5
Oxygenates	.534	.597	.305	.648	.905
Wax ^c	5.54	9.62	4.24	3.78	9.79
Yield (g/Nm ³ H ₂ + CO Converted)					
CH ₄	6.11	7.29	5.23	6.76	6.69
C ₂ -C ₄ Hydrocarbons	24.6	25.7	22.2	25.4	27.2
C ₅ -C ₁₁ Hydrocarbons	38.2	46.2	40.3	41.3	56.7
C ₁₂ + Hydrocarbons	113.	145.	180.	110.	118.
Wax ^c	79.4	108.	113.	66.9	101.
Oxygenates	7.66	6.67	8.13	11.5	9.32
Total	189.	231.	256.	195.	218.
1+2 Olefins/n-Paraffin Ratio					
C ₂	2.07	2.45	3.99	3.56	2.29
C ₃	5.63	5.79	4.48	4.35	4.47
C ₄	4.13	4.44	3.33	3.27	3.42
C ₈	2.59	4.05	2.79	2.47	2.65
C ₁₀	2.61	3.78	2.69	2.24	2.42

^a Based on unreduced catalyst.

^c Unanalyzed wax withdrawn from reactor

^b Based on static slurry volume

Table 12 (cont'd). Summary of results for slurry run SB-07-0458.

Weight % of Hydrocarbons	Period				
	1	2	3	4	5
CH ₄	4.58	3.96	5.44	3.10	2.76
Ethane	4.78	2.56	3.73	4.03	1.57
Ethylene	5.34	3.73	4.85	3.38	2.79
Propane	1.30	.988	1.03	.694	.644
Propylene	5.05	4.27	5.19	3.26	3.15
n-Butane	1.74	1.09	1.12	.792	.737
1+2 Butenes	6.05	3.79	4.43	2.80	2.73
C ₄ Isomers	.755	.421	.487	.289	.267
n-Pentane	1.57	1.36	1.44	1.08	.990
1+2 Pentenes	3.92	3.50	4.01	2.72	2.64
C ₅ Isomers	.245	.211	.236	1.18	.741
n-Hexane	1.10	1.07	1.40	2.24	.817
1+2 Hexenes	3.90	2.75	3.74	3.92	2.41
C ₆ Isomers	1.10	.514	.844	2.07	.588
n-Heptane	.729	.632	.816	.859	.685
1+2 Heptenes	2.26	1.64	2.07	1.87	1.67
C ₇ Isomers	.715	.413	.561	.713	.513
n-Octane	.481	.671	.659	.365	.526
1+2 Octenes	1.43	1.71	1.73	1.18	1.45
C ₈ Isomers	.297	.278	.322	.0858	.222
n-Nonane	.418	.644	.631	.423	.548
1+2 Nonenes	.896	1.65	1.62	.989	1.36
C ₉ Isomers	.0764	.135	.204	.0756	.105
n-Decane	.503	.681	.718	.528	.608
1+2 Decenes	1.13	1.81	1.92	1.33	1.57
C ₁₀ Isomers	.105	.166	.299	.120	.158
n-Undecane	.405	.610	.630	.441	.516
1+2 Undecenes	1.25	1.85	2.04	1.59	1.65
C ₁₁ Isomers	.136	.205	.288	.160	.194
C ₂ -C ₄	25.0	16.8	20.9	15.3	11.9
C ₅ -C ₁₁	22.7	22.5	26.2	23.9	20.0
C ₁₂ +	47.7	57.2	47.9	58.1	65.8
Wax ^c	34.8	31.6	20.7	32.6	41.9

^c Unanalyzed wax withdrawn from reactor

Table 12 (cont'd). Summary of results for slurry run SB-07-0458.

Period		6	7	8	9	10
Weight % of Hydrocarbons						
CH ₄		3.36	3.25	2.11	3.68	3.21
Ethane		1.75	1.10	.546	.914	1.14
Ethylene		3.38	2.51	2.03	3.03	2.44
Propane		.667	.618	.601	.984	.924
Propylene		3.58	3.41	2.57	4.09	3.94
n-Butane		.773	.671	.697	1.06	.990
1+2 Butenes		3.08	2.88	2.24	3.36	3.27
C ₄ Isomers		.292	.253	.263	.400	.335
n-Pentane		1.08	.928	.920	1.36	1.20
1+2 Pentenes		2.97	2.71	2.19	3.10	3.07
C ₅ Isomers		.577	.140	.620	.813	.600
n-Hexane		.758	.679	.435	1.22	1.05
1+2 Hexenes		2.19	2.41	1.69	2.18	2.99
C ₆ Isomers		.817	.648	.484	.519	.350
n-Heptane		.528	.486	.443	.597	.954
1+2 Heptenes		1.33	1.42	1.22	1.46	2.13
C ₇ Isomers		.298	.252	.388	.345	.258
n-Octane		.601	.436	.393	.654	1.01
1+2 Octenes		1.53	1.74	1.08	1.59	2.62
C ₈ Isomers		.255	.191	.0587	.109	.180
n-Nonane		.672	.500	.450	.816	1.03
1+2 Nonenes		1.65	1.86	1.14	1.65	2.49
C ₉ Isomers		.175	.124	.0540	.0874	.125
n-Decane		.728	.580	.582	.895	1.04
1+2 Decenes		1.87	2.16	1.55	1.97	2.48
C ₁₀ Isomers		.242	.182	.0822	.122	.165
n-Undecane		.608	.597	.535	.754	.959
1+2 Undecenes		1.95	2.27	1.81	2.10	2.31
C ₁₁ Isomers		.221	.254	.138	.152	.176
C ₂ -C ₄		13.5	11.5	8.94	13.8	13.0
C ₅ -C ₁₁		21.1	20.6	16.2	22.5	27.2
C ₁₂ +		62.4	65.0	73.0	60.5	56.6
Wax ^c		43.7	47.9	45.7	36.5	48.3

^c Unanalyzed wax withdrawn from reactor

Table 13. Major events in run SB-07-0458.

TOS (h)	Event
-28	Catalyst pretreatment
0	Initiate run
4	Wax plug in reactor feed line repaired
5	Achieved initial process conditions: $T = 250^{\circ}\text{C}$, $P = 1.48 \text{ MPa}$, $SV = 2.2 \text{ Nl/g-cat}\cdot\text{h}$, $(\text{H}_2/\text{CO}) = 1.05$
53	Changed process conditions: $T = 250^{\circ}\text{C}$, $P = 1.48 \text{ MPa}$, $SV = 1.1 \text{ Nl/g-cat}\cdot\text{h}$, $(\text{H}_2/\text{CO}) = 1.05$
100	Changed process conditions: $T = 265^{\circ}\text{C}$, $P = 1.48 \text{ MPa}$, $SV = 2.1 \text{ Nl/g-cat}\cdot\text{h}$, $(\text{H}_2/\text{CO}) = 1.05$
148	Changed process conditions: $T = 250^{\circ}\text{C}$, $P = 1.48 \text{ MPa}$, $SV = 2.1 \text{ Nl/g-cat}\cdot\text{h}$, $(\text{H}_2/\text{CO}) = 0.71$
196	Changed process conditions: $T = 250^{\circ}\text{C}$, $P = 1.48 \text{ MPa}$, $SV = 1.1 \text{ Nl/g-cat}\cdot\text{h}$, $(\text{H}_2/\text{CO}) = 0.74$
244	Changed process conditions: $T = 265^{\circ}\text{C}$, $P = 1.48 \text{ MPa}$, $SV = 2.2 \text{ Nl/g-cat}\cdot\text{h}$, $(\text{H}_2/\text{CO}) = 0.70$
292	Changed process conditions: $T = 265^{\circ}\text{C}$, $P = 1.48 \text{ MPa}$, $SV = 1.1 \text{ Nl/g-cat}\cdot\text{h}$, $(\text{H}_2/\text{CO}) = 0.72$
340	Changed process conditions: $T = 235^{\circ}\text{C}$, $P = 1.48 \text{ MPa}$, $SV = 1.1 \text{ Nl/g-cat}\cdot\text{h}$, $(\text{H}_2/\text{CO}) = 0.71$
388	Changed process conditions: $T = 250^{\circ}\text{C}$, $P = 1.48 \text{ MPa}$, $SV = 2.2 \text{ Nl/g-cat}\cdot\text{h}$, $(\text{H}_2/\text{CO}) = 1.06$
436	Changed process conditions: $T = 265^{\circ}\text{C}$, $P = 2.96 \text{ MPa}$, $SV = 2.0 \text{ Nl/g-cat}\cdot\text{h}$, $(\text{H}_2/\text{CO}) = 0.73$
458	End of run SB-07-0458

Table 14. Wax and solids inventory for run SB-07-0458.

TOS (h)	Event
-48	Slurry loading: 400 g wax, 30.02 g solids
-1	Wax removal following reduction: 126 g wax, 0.35 g solids
51	Wax removal: 34 g wax, 0.06 g solids
98	Wax removal: 38 g wax, 0.0 g solids
146	Wax removal: 35 g wax, 0.02 g solids
194	Wax removal: 40 g wax, 0.14 g solids
242	Wax removal: 57 g wax, 0.53 g solids
290	Wax removal: 121 g wax, 0.45 g solids
338	Wax removal: 112 g wax, 0.61 g solids
386	Wax removal: 47 g wax, 0.54 g solids
434	Wax removal: 68 g wax, 0.62 g solids
458	Wax removal: 95 g wax, 1.02 g solids
466	End of run: 245 g wax, 18.18 g solids recovered from reactor. 90 % wax recovery, 76 % solids recovery

Table 15. Nominal ranges of process variables studied in runs SA-25-3657 and SA-07-0468.

Temperature ($^{\circ}\text{C}$):	235, 250, 265
Pressure (MPa):	1.48, 2.96
Space Velocity ($\text{Nl/g-cat}\cdot\text{h}$):	1.0, 2.0, 4.0
Molar (H_2/CO) Feed Ratio:	0.67, 1.0

Table 16. Summary of results for slurry run SA-07-0468.

Catalyst: 29.5 g^a, 100 Fe/.3 Cu/0.5 K

Slurry liquid: 270 g, FT-300

Reactor volume: 385. cc^b

Period	1	2	3	4	5	6
Date	2/18/88	2/20/88	2/22/88	2/24/88	2/24/88	2/24/88
Time on Stream (h)	40.5	86.0	135.0	183.0	215.0	254.0
Balance Duration (h)	6.0	6.0	6.0	6.0	17.0	6.0
Average Temperature (°C)	250.	250.	265.	235.	235.	235.
Pressure (MPa)	1.48	1.48	1.48	1.48	1.48	1.48
H ₂ /CO Feed Ratio	1.10	.976	1.03	.957	.985	.653
Space Velocity (NI/g-cat·h) ^a	2.04	4.05	4.00	2.08	4.18	1.02
Space Velocity (NI/g-Fe·h)	2.94	5.84	5.76	3.00	6.03	1.47
GHSV (h ⁻¹) ^b	156.	301.	291.	144.	277.	66.4
CO Conversion (%)	91.7	70.9	71.4	33.5	15.3	38.5
H ₂ +CO Conversion (%)	74.8	58.4	55.5	28.4	12.7	35.6
H ₂ /CO Usage	.710	.628	.576	.661	.649	.530
STY (mols H ₂ +CO/g-cat·h) ^a	.068	.106	.099	.026	.024	.016
P _{CO₂} · P _{H₂} /P _{CO} · P _{H₂O}	39.7	20.3	27.8	6.86	2.42	10.1
Weight % of Outlet						
H ₂	3.11	3.52	4.03	4.98	6.01	3.01
H ₂ O	3.34	1.86	1.56	1.47	1.53	.827
CO	8.07	26.8	26.1	62.6	79.8	57.3
CO ₂	60.6	50.7	49.2	22.4	8.67	27.9
Hydrocarbons	12.9	8.54	8.69	3.01	2.44	3.60
Oxygenates	1.04	.638	.801	.341	.207	.183
Wax ^c	10.9	7.90	9.64	5.26	1.31	7.21
Yield (g/Nm ³ H ₂ + CO Converted)						
CH ₄	13.4	7.06	8.37	5.20	5.82	4.90
C ₂ -C ₄ Hydrocarbons	43.6	35.9	38.0	24.9	31.6	27.1
C ₅ -C ₁₁ Hydrocarbons	39.9	40.1	44.6	30.4	58.7	30.7
C ₁₂ + Hydrocarbons	98.7	110.	132.	137.	100.	184.
Wax ^c	89.6	92.7	118.	126.	68.6	164.
Oxygenates	8.55	7.48	9.76	8.16	10.9	4.17
Total	204.	200.	233.	206.	207.	251.
1+2 Olefins/n-Paraffin Ratio						
C ₂	1.26	2.21	2.51	6.50	1.66	4.32
C ₃	6.06	6.33	6.55	5.32	5.29	5.95
C ₄	5.10	4.98	5.13	4.07	4.05	4.46
C ₈	3.73	4.92	3.85	2.83	1.92	2.93
C ₁₀	3.49	5.33	4.46	3.08	3.06	3.69

^a Based on unreduced catalyst^c Unanalyzed wax withdrawn from reactor^b Based on static slurry volume

Table 16 (cont'd). Summary of results for slurry run SA-07-0468.

Period	7	8	9	10	11
Date	2/29/88	3/02/88	3/04/88	3/06/88	3/07/88
Time on Stream (h)	302.5	351.0	390.5	437.0	460.0
Balance Duration (h)	6.0	6.0	6.0	6.0	6.0
Average Temperature (°C)	250.	250.	265.	250.	265.
Pressure (MPa)	1.48	1.48	1.48	1.48	2.96
H ₂ /CO Feed Ratio	.653	.689	.641	1.03	.640
Space Velocity (NI/g-cat·h) ^a	1.01	2.05	2.03	2.03	2.04
Space Velocity (NI/g-Fe·h)	1.46	2.96	2.93	2.93	2.94
GHSV (h ⁻¹) ^b	65.5	129.	126.	124.	124.
CO Conversion (%)	57.4	26.2	29.8	24.6	42.4
H ₂ +CO Conversion (%)	54.2	24.0	28.2	17.4	38.9
H ₂ /CO Usage	.561	.548	.550	.432	.503
STY (mols H ₂ +CO/g-cat·h) ^a	.024	.022	.026	.016	.035
P _{CO₂} · P _{H₂} /P _{CO} · P _{H₂O}	26.5	12.4	14.8	8.76	12.3
Weight % of Outlet					
H ₂	2.34	3.86	3.30	6.33	3.02
H ₂ O	.478	.421	.399	.865	.715
CO	41.8	72.5	67.4	72.0	56.6
CO ₂	39.9	17.3	21.2	15.2	29.1
Hydrocarbons	6.86	2.66	3.49	3.15	5.56
Oxygenates	.422	.199	.226	.261	.525
Wax ^c	8.15	3.05	3.95	2.18	4.47
Yield (g/Nm ³ H ₂ + CO Converted)					
CH ₄	5.24	5.74	7.74	9.00	7.12
C ₂ -C ₄ Hydrocarbons	27.4	26.7	29.8	34.2	30.8
C ₅ -C ₁₁ Hydrocarbons	41.5	36.7	42.0	52.7	53.5
C ₁₂ + Hydrocarbons	139.	110.	130.	102.	108.
Wax ^c	116.	95.4	111.	81.2	89.0
Oxygenates	6.00	6.23	6.37	9.71	10.5
Total	219.	185.	216.	208.	210.
1+2 Olefins/n-Paraffin Ratio					
C ₂	2.12	4.83	5.47	4.29	3.24
C ₃	6.29	5.97	6.10	4.44	4.04
C ₄	4.73	4.31	4.32	3.22	2.95
C ₈	3.54	3.34	3.08	2.35	2.03
C ₁₀	3.65	3.11	3.17	1.95	2.01

^a Based on unreduced catalyst

^c Unanalyzed wax withdrawn from reactor

^b Based on static slurry volume

Table 16 (cont'd). Summary of results for slurry run SA-07-0468.

Period	1	2	3	4	5	6
Weight % of Hydrocarbons						
CH ₄	6.86	3.66	3.75	2.63	2.97	1.99
Ethane	3.32	2.09	1.83	.507	2.47	.794
Ethylene	3.90	4.29	4.27	3.07	3.82	3.20
Propane	1.20	.891	.798	.765	.822	.538
Propylene	6.94	5.39	4.99	3.88	4.15	3.06
n-Butane	1.07	.928	.782	.806	.898	.590
1+2 Butenes	5.27	4.46	3.88	3.17	3.51	2.54
C ₄ Isomers	.595	.571	.466	.381	.433	.284
n-Pentane	1.31	1.12	1.08	1.10	1.34	.850
1+2 Pentenes	4.22	3.60	3.31	3.02	3.66	2.43
C ₅ Isomers	.288	.238	.222	.229	.283	.157
n-Hexane	.846	.771	.742	1.66	2.50	.820
1+2 Hexenes	2.61	2.31	2.47	1.95	4.06	1.86
C ₆ Isomers	.918	.559	.577	.611	1.20	.528
n-Heptane	.464	.376	.451	.438	1.50	.402
1+2 Heptenes	1.56	1.17	1.47	1.26	3.90	1.19
C ₇ Isomers	.356	.392	.490	.412	1.02	.411
n-Octane	.396	.293	.391	.258	.998	.199
1+2 Octenes	1.45	1.41	1.48	.717	1.88	.571
C ₈ Isomers	.360	.253	.299	.0773	.268	.0669
n-Nonane	.357	.331	.363	.196	.384	.145
1+2 Nonenes	1.31	1.84	1.59	.580	1.08	.505
C ₉ Isomers	.180	.221	.285	.0779	.168	.0555
n-Decane	.402	.424	.388	.288	.570	.208
1+2 Decenes	1.38	2.23	1.70	.876	1.72	.757
C ₁₀ Isomers	.182	.267	.332	.122	.243	.0812
n-Undecane	.381	.433	.383	.314	.531	.201
1+2 Undecenes	1.29	2.24	1.60	1.02	2.22	.915
C ₁₁ Isomers	.153	.321	.347	.164	.361	.116
C ₂ -C ₄	22.3	18.6	17.0	12.6	16.1	11.0
C ₅ -C ₁₁	20.4	20.8	20.0	15.4	29.9	12.5
C ₁₂ +	50.4	57.0	59.3	69.5	51.3	74.6
Wax ^c	45.8	48.1	52.6	63.6	34.9	66.7

^c Unanalyzed wax withdrawn from reactor

Table 16 (cont'd). Summary of results for slurry run SA-07-0468.

Period		7	8	9	10	11
Weight % of Hydrocarbons						
CH ₄		2.46	3.21	3.69	4.54	3.56
Ethane		1.60	.853	.712	1.03	1.18
Ethylene		3.16	3.84	3.64	4.12	3.57
Propane		.586	.792	.752	1.17	1.11
Propylene		3.52	4.51	4.38	4.98	4.29
n-Butane		.652	.877	.843	1.32	1.25
1+2 Butenes		2.98	3.64	3.51	4.10	3.57
C ₄ Isomers		.325	.429	.392	.547	.456
n-Pentane		.932	1.31	1.25	1.75	1.64
1+2 Pentenes		2.90	3.48	3.28	3.88	3.40
C ₅ Isomers		.165	.266	.193	1.45	1.21
n-Hexane		.999	.900	1.29	1.14	.882
1+2 Hexenes		2.25	2.73	1.98	3.31	2.50
C ₆ Isomers		.616	.900	.610	1.34	.686
n-Heptane		.496	.706	.544	1.42	.984
1+2 Heptenes		1.59	1.90	1.39	2.97	1.82
C ₇ Isomers		.442	.651	.375	1.30	.469
n-Octane		.314	.397	.344	.521	.865
1+2 Octenes		1.09	1.30	1.04	1.20	1.73
C ₈ Isomers		.138	.125	.0799	.0853	.211
n-Nonane		.353	.305	.443	.454	1.05
1+2 Nonenes		1.32	.889	1.33	.820	1.90
C ₉ Isomers		.0939	.0558	.0866	.0609	.154
n-Decane		.539	.480	.633	.713	1.15
1+2 Decenes		1.94	1.47	1.98	1.37	2.28
C ₁₀ Isomers		.179	.123	.163	.157	.246
n-Undecane		.622	.475	.540	.601	.943
1+2 Undecenes		2.23	1.86	2.30	1.79	2.40
C ₁₁ Isomers		.245	.193	.201	.218	.248
C ₂ -C ₄		12.8	14.9	14.2	17.3	15.4
C ₅ -C ₁₁		19.5	20.5	20.0	26.6	26.8
C ₁₂ +		65.4	61.4	62.1	51.9	54.4
Wax ^c		54.3	53.4	53.1	40.9	44.5

^c Unanalyzed wax withdrawn from reactor

Table 17. Major events in run SA-07-0468.

TOS (h)	Event
-20	Catalyst pretreatment
0	Initiate run
4	Achieve initial process conditions: $T = 250^{\circ}\text{C}$, $P = 1.48 \text{ MPa}$, $SV = 2.0 \text{ NI/g-cat}\cdot\text{h}$, Feed (H_2/CO) = 1.0
19-39	Problems with hydrogen flow rate
39	Switched from pure gases to premixed gas
47	Replaced hydrogen flow controller; switched to pure gases
47-52	Problems with hydrogen flow rate
52	Switched from pure gases to premixed gas
68	Changed process conditions: $T = 250^{\circ}\text{C}$, $P = 1.48 \text{ MPa}$, $SV = 4.0 \text{ NI/g-cat}\cdot\text{h}$, Feed (H_2/CO) = 1.0
78	Replaced feed gas cylinder. Gas not properly mixed; 95% hydrogen
79	Replaced problem cylinder, Feed (H_2/CO) = 1.0
93	Changed process conditions: $T = 265^{\circ}\text{C}$, $P = 1.48 \text{ MPa}$, $SV = 4.0 \text{ NI/g-cat}\cdot\text{h}$, Feed (H_2/CO) = 1.0
139	15°C rise in temperature of reflux condenser
141	Repeated wax removal twice due to excessive wax production
143	Changed process conditions: $T = 235^{\circ}\text{C}$, $P = 1.48 \text{ MPa}$, $SV = 2.0 \text{ NI/g-cat}\cdot\text{h}$, Feed (H_2/CO) = 1.0
191	Changed process conditions: $T = 235^{\circ}\text{C}$, $P = 1.48 \text{ MPa}$, $SV = 4.0 \text{ NI/g-cat}\cdot\text{h}$, Feed (H_2/CO) = 1.0
233	Changed process conditions: $T = 235^{\circ}\text{C}$, $P = 1.48 \text{ MPa}$, $SV = 1.0 \text{ NI/g-cat}\cdot\text{h}$, Feed (H_2/CO) = 0.66
261	Changed process conditions: $T = 250^{\circ}\text{C}$, $P = 1.48 \text{ MPa}$, $SV = 1.0 \text{ NI/g-cat}\cdot\text{h}$, Feed (H_2/CO) = 0.64
311	Changed process conditions: $T = 250^{\circ}\text{C}$, $P = 1.48 \text{ MPa}$, $SV = 2.0 \text{ NI/g-cat}\cdot\text{h}$, Feed (H_2/CO) = 0.69
359	Changed process conditions: $T = 265^{\circ}\text{C}$, $P = 1.48 \text{ MPa}$, $SV = 2.0 \text{ NI/g-cat}\cdot\text{h}$, Feed (H_2/CO) = 0.64
398	Changed process conditions: $T = 250^{\circ}\text{C}$, $P = 1.48 \text{ MPa}$, $SV = 2.0 \text{ NI/g-cat}\cdot\text{h}$, Feed (H_2/CO) = 1.0
444	Changed process conditions: $T = 265^{\circ}\text{C}$, $P = 2.96 \text{ MPa}$, $SV = 2.0 \text{ NI/g-cat}\cdot\text{h}$, Feed (H_2/CO) = 0.64
466	End of Run SA-07-0468

Table 18. Wax and solids inventory for run SA-07-0468.

TOS (h)	Event
-48	Slurry loading: 400 <i>g</i> wax, 30.25 <i>g</i> solids
-1	Wax removal following reduction: 156 <i>g</i> wax, 0.80 <i>g</i> solids
64	Wax removal: 241 <i>g</i> wax, 0.86 <i>g</i> solids
92	Wax removal: 162 <i>g</i> wax, 0.55 <i>g</i> solids
141	Wax removal: 342 <i>g</i> wax, 1.37 <i>g</i> solids
189	Wax removal: 94 <i>g</i> wax, 1.16 <i>g</i> solids
231	Wax removal: 38 <i>g</i> wax, 0.40 <i>g</i> solids
260	Wax removal: 40 <i>g</i> wax, 0.23 <i>g</i> solids
309	Wax removal: 75 <i>g</i> wax, 0.61 <i>g</i> solids
357	Wax removal: 54 <i>g</i> wax, 0.39 <i>g</i> solids
396	Wax removal: 72 <i>g</i> wax, 0.37 <i>g</i> solids
443	Wax removal: 31 <i>g</i> wax, 0.14 <i>g</i> solids
466	Wax removal: 38 <i>g</i> wax, 0.11 <i>g</i> solids
466	End of run: 241 <i>g</i> wax, 21.65 <i>g</i> solids recovered from reactor. 98 % wax recovery, 94 % solids recovery

Table 19. Summary of results for slurry run SA-25-3657.
Catalyst: 38.4 g^a, 100 Fe/3 Cu/0.2 K
Slurry liquid: 307 g, n-Octacosane
Reactor volume: 438. cc^b

Period	1	2	3	4	5	6	7	8
Date	1/3/88	1/5/88	1/8/88	1/10/88	1/12/88	1/12/88	1/16/88	1/18/88
Time on Stream (h)	44.0	91.0	158.5	206.0	254.0	302.0	350.0	398.0
Balance Duration (h)	6.0	6.0	6.0	6.0	6.0	6.0	6.0	6.0
Average Temperature (°C)	250.	250.	235.	250.	250.	250.	265.	235.
Pressure (MPa)	1.48	1.48	1.48	1.48	1.48	1.48	1.48	1.48
H ₂ /CO Feed Ratio	.994	.994	.980	1.01	.663	.682	.678	.669
Space Velocity (Nl/g-cat·h) ^a	2.02	4.03	2.01	2.00	1.01	2.01	2.02	1.01
Space Velocity (Nl/g-Fe·h)	2.96	5.93	2.95	2.94	1.48	2.96	2.96	1.49
GHSV (h ⁻¹) ^b	177.	350.	174.	173.	86.0	171.	171.	85.6
CO Conversion (%)	93.9	47.6	15.5	28.3	48.3	16.5	27.8	10.8
H ₂ +CO Conversion (%)	83.0	46.7	21.4	28.5	44.8	18.6	29.3	13.9
H ₂ /CO Usage	.762	.957	1.74	1.02	.543	.893	.770	1.14
STY (mole H ₂ +CO/g-cat·h) ^a	.075	.094	.019	.025	.020	.017	.026	.006
P _{CO₂} · P _{H₂} / P _{CO} · P _{H₂O}	22.6	1.53	.321	.647	.806	.442	1.01	.434
Weight % of Outlet								
H ₂	1.93	3.68	4.82	5.08	3.33	3.79	3.24	3.72
H ₂ O	5.30	6.93	5.46	6.49	7.62	3.37	3.67	2.78
CO	5.86	49.7	79.6	70.3	59.6	82.3	70.2	84.7
CO ₂	64.0	25.2	5.08	10.2	19.4	5.69	14.1	4.82
Hydrocarbons	19.7	10.4	3.55	4.57	6.17	3.05	5.51	2.41
Oxygenates	.647	.494	.176	.129	.220	.136	.202	.104
Wax ^c	2.50	3.59	1.36	3.24	3.68	1.65	3.09	1.48
Yield (g/Nm ³ H ₂ + CO Converted)								
CH ₄	16.2	9.06	6.93	8.46	4.52	6.11	7.66	8.89
C ₂ -C ₄ Hydrocarbons	62.6	44.1	40.5	37.7	29.4	39.2	37.9	56.1
C ₅ -C ₁₁ Hydrocarbons	68.0	55.3	44.4	39.9	39.6	53.1	45.3	40.7
C ₁₂ + Hydrocarbons	27.5	89.0	62.1	87.8	69.7	91.6	134.	115.
Wax ^c	19.6	50.8	42.6	72.1	53.5	66.7	80.7	83.8
Oxygenates	5.07	7.00	5.51	2.87	3.20	5.59	5.29	5.87
Total	179.	204.	159.	177.	146.	196.	230.	226.
1+2 Olefins/n-Paraffin Ratio								
C ₂	.242	1.40	1.61	2.72	1.20	1.16	1.40	1.29
C ₃	2.57	6.47	6.01	6.57	6.97	7.48	8.27	4.04
C ₄	3.06	5.37	4.54	5.69	5.80	5.92	6.48	4.35
C ₅	.697	2.60	2.61	2.75	3.08	2.52	3.46	1.25
C ₁₀	.345	1.86	2.82	2.64	3.17	2.61	4.33	2.19

^a Based on unreduced catalyst

^c Unanalyzed wax withdrawn from reactor

^b Based on static slurry volume

Table 19 (cont'd). Summary of results for slurry run SA-25-3657.

Period	1	2	3	4	5	6	7	8
Weight % of Hydrocarbons								
CH ₄	9.31	4.59	4.50	4.87	3.16	3.21	3.41	4.04
Ethane	7.22	2.59	3.82	1.59	3.11	4.77	2.95	4.28
Ethylene	1.63	3.39	5.75	4.02	3.49	5.16	3.85	5.14
Propane	4.29	1.19	1.29	1.16	.934	.675	.586	1.56
Propylene	10.5	7.35	7.37	7.29	6.21	4.82	4.63	5.99
n-Butane	2.82	1.16	1.39	1.08	.958	.719	.616	1.43
1+2 Butenes	8.32	6.03	6.08	5.93	5.36	4.11	3.85	6.01
C ₄ Isomers	1.11	.639	.604	.592	.468	.388	.369	1.05
n-Pentane	3.11	1.64	1.68	1.52	1.18	1.04	.963	1.36
1+2 Pentenes	6.75	6.30	6.93	5.18	4.18	3.72	3.54	4.82
C ₅ Isomers	.841	.757	1.05	.384	.300	.277	.260	.430
n-Hexane	2.71	1.14	1.26	.952	1.05	1.62	.911	1.59
1+2 Hexenes	3.87	2.88	3.86	3.13	4.52	4.50	2.94	1.99
C ₆ Isomers	.653	.620	.851	.661	.899	.988	.687	.640
n-Heptane	2.52	.731	.863	.898	1.09	1.46	.659	1.02
1+2 Heptenes	2.19	1.69	2.39	1.83	2.83	2.98	1.81	1.27
C ₇ Isomers	.642	.432	.609	.490	.804	.801	.530	.419
n-Octane	2.44	.609	.550	.466	.631	.676	.339	.429
1+2 Octenes	1.67	1.56	1.41	1.26	1.91	1.67	1.15	.527
C ₈ Isomers	.636	.250	.329	.0868	.651	.157	.291	.423
n-Nonane	2.31	.737	.304	.303	.292	.400	.179	.154
1+2 Nonenes	1.29	1.65	1.97	1.06	1.39	1.30	1.06	.465
C ₉ Isomers	.468	.251	.144	.111	.0959	.242	.0732	.0219
n-Decane	2.61	1.00	.588	.542	.587	.668	.365	.375
1+2 Decenes	.887	1.84	1.64	1.41	1.84	1.72	1.56	.808
C ₁₀ Isomers	.514	.410	.280	.172	.178	.383	.143	.0655
n-Undecane	1.64	1.18	.810	.725	.877	.902	.597	.504
1+2 Undecenes	.746	1.80	1.85	1.54	2.04	1.95	1.87	1.05
C ₁₁ Isomers	.483	.526	.366	.234	.287	.488	.243	.107
C ₂ -C ₄	35.9	22.3	26.3	21.7	20.5	20.6	16.9	25.5
C ₅ -C ₁₁	39.0	28.0	28.8	23.0	27.6	27.9	20.2	18.5
C ₁₂ +	15.8	45.1	40.4	50.5	48.7	48.2	59.6	52.0
Wax ^c	11.2	25.7	27.7	41.5	37.3	35.1	35.9	38.1

^c Unanalyzed wax withdrawn from reactor

Table 20. Major events in run SA-25-3657.

TOS (h)	Event
-28	Catalyst pretreatment
0	Initiate run
4	Achieve initial process conditions: $T = 250^{\circ}\text{C}$, $P = 1.48 \text{ MPa}$, $SV = 2.0 \text{ NI/g-cat}\cdot\text{h}$, Feed (H_2/CO) = 1.0
51	Change process conditions: $T = 250^{\circ}\text{C}$, $P = 1.48 \text{ MPa}$ $SV = 4.0 \text{ NI/g-cat}\cdot\text{h}$, Feed (H_2/CO) = 1.0
94	Change process conditions: $T = 235^{\circ}\text{C}$, $P = 1.48 \text{ MPa}$ $SV = 2.0 \text{ NI/g-cat}\cdot\text{h}$, Feed (H_2/CO) = 1.0
129	Loss of reactor power
134	Power to reactor restored
138	Achieve desired process conditions
166	Change process conditions: $T = 250^{\circ}\text{C}$, $P = 1.48 \text{ MPa}$ $SV = 2.0 \text{ NI/g-cat}\cdot\text{h}$, Feed (H_2/CO) = 1.0
214	Change process conditions: $T = 250^{\circ}\text{C}$, $P = 1.48 \text{ MPa}$ $SV = 1.0 \text{ NI/g-cat}\cdot\text{h}$, Feed (H_2/CO) = 0.67
260	Leak in reactor feed valve discovered and repaired
262	Change process conditions: $T = 250^{\circ}\text{C}$, $P = 1.48 \text{ MPa}$ $SV = 2.0 \text{ NI/g-cat}\cdot\text{h}$, Feed (H_2/CO) = 0.68
310	Change process conditions: $T = 265^{\circ}\text{C}$, $P = 1.48 \text{ MPa}$ $SV = 2.0 \text{ NI/g-cat}\cdot\text{h}$, Feed (H_2/CO) = 0.68
357	Wax plug in reactor feed line repaired
358	Change process conditions: $T = 235^{\circ}\text{C}$, $P = 1.48 \text{ MPa}$ $SV = 1.0 \text{ NI/g-cat}\cdot\text{h}$, Feed (H_2/CO) = 0.67
406	Change process conditions: $T = 265^{\circ}\text{C}$, $P = 2.96 \text{ MPa}$ $SV = 2.0 \text{ NI/g-cat}\cdot\text{h}$, Feed (H_2/CO) = 0.67
430	End of Run SA-25-3657

Table 21. Wax and solids inventory for run SA-25-3657.

TOS (h)	Event
-48	Slurry loading: 424 g wax, 38.60 g solids
-1	Wax removal following reduction: 120 g wax, 0.24 g solids
50	Wax removal: 57 g wax, 0.55 g solids
93	Wax removal: 161 g wax, 0.26 g solids
164	Wax removal: 90 g wax, 0.29 g solids
212	Wax removal: 71 g wax, 0.13 g solids
261	Wax removal: 36 g wax, 0.09 g solids
308	Wax removal: 43 g wax, 0.07 g solids
355	Wax removal: 81 g wax, 0.16 g solids
404	Wax removal: 20 g wax, 0.05 g solids
430	Wax removal: 60 g wax, 0.11 g solids
430	End of run: 289 g wax, 33.06 g solids recovered from reactor. 95 % wax recovery, 96 % solids recovery

Table 22. Summary of results for fixed bed run FA-01-0128.

Catalyst: 5.50 g^a, United Catalyst' C-73
 Catalyst volume: 2.4 cc
 Diluent: 32.3 g, Glass beads
 Diluent Volume: 23.0 cc

Period	1	2	3	4	5	6	7
Date	1/14/88	1/15/88	1/16/88	1/17/88	1/18/88	1/19/88	1/20/88
Time on Stream (h)	44.5	69.0	82.5	106.5	130.5	154.5	179.5
Balance Duration (h)	6.0	6.0	6.0	7.0	7.0	6.5	6.0
Average Temperature (°C)	232.	247.	248.	250.	235.	233.	235.
Maximum Δ Temperature (°C) ^b	2.50	5.70	6.00	6.00	6.00	3.00	29.0
Pressure (MPa)	.791	.791	.791	1.58	1.58	.791	1.48
H ₂ /CO Feed Ratio	1.10	1.10	1.10	1.10	1.10	1.10	1.10
Space Velocity (NI/g-cat·h) ^a	1.47	1.47	2.98	.749	.743	1.47	1.96
Space Velocity (NI/g-Fe·h)	2.19	2.19	4.45	1.12	1.11	2.19	2.92
GHSV (h ⁻¹) ^c	310	310	630	159	157	311	414
CO Conversion (%)	26.2	73.3	44.2	99.1	94.3	41.3	96.6
H ₂ +CO Conversion (%)	22.3	60.0	37.2	85.9	78.5	33.2	80.9
H ₂ /CO Usage	.79	.72	.76	.82	.74	.69	.76
STY (mols H ₂ +CO/g-cat·h) ^a	.015	.039	.049	.029	.026	.022	.071
P _{CO₂} · P _{H₂} /P _{CO} · P _{H₂O}	2.12	13.3	5.21	180.	34.0	7.13	77.5
Weight % of Outlet							
H ₂	6.11	3.99	5.29	1.91	2.63	5.42	2.56
H ₂ O	3.21	3.31	3.02	5.01	5.52	2.27	3.77
CO	70.5	25.9	54.0	.814	5.26	54.4	3.30
CO ₂	13.8	50.4	28.3	67.6	65.9	28.6	66.4
Hydrocarbons	5.32	15.5	8.94	23.3	17.9	8.57	21.6
Oxygenates	.494	.811	.386	.797	1.01	.663	.575
Wax ^d	.602	.0403	.0198	.603	1.83	.0948	1.76
Yield (g/Nm ³ H ₂ + CO Converted)							
CH ₄	22.0	26.0	25.9	33.3	26.0	25.7	22.9
C ₂ -C ₄ Hydrocarbons	70.2	69.2	62.7	80.1	70.4	74.6	66.3
C ₅ -C ₁₁ Hydrocarbons	53.4	60.4	51.4	54.8	48.3	57.8	65.0
C ₁₂ + Hydrocarbons	19.8	3.81	8.53	10.5	16.9	9.56	23.9
Wax ^d	16.8	.413	.329	4.52	15.0	1.83	13.4
Oxygenates	13.8	8.31	6.39	5.97	8.24	12.8	4.38
Total	179.	168.	155.	185.	170.	180.	183.
1+2 Olefins/n-Paraffin Ratio							
C ₂	1.32	.564	.890	.524	.673	.945	.914
C ₃	5.15	4.44	4.61	3.83	3.75	3.43	5.74
C ₄	4.07	3.70	3.95	3.25	3.09	3.17	4.84
C ₈	2.38	1.87	2.22	1.92	2.01	1.98	2.67
C ₁₀	2.30	1.47	2.05	1.57	1.80	2.40	2.50

^a Based on unreduced catalyst^b Maximum axial temperature difference

Table 22 (cont'd). Summary of results for fixed bed run FA-01-0128.

Period	1	2	3	4	5	6	7
Weight % of Hydrocarbons							
CH ₄	13.3	16.3	17.4	18.7	16.1	15.3	12.9
Ethane	7.79	8.91	7.03	9.00	7.76	8.41	5.44
Ethylene	9.57	4.69	5.84	4.40	4.88	7.42	4.64
Propane	2.31	3.12	2.92	3.87	3.77	3.46	2.27
Propylene	11.3	13.2	12.8	14.2	13.5	11.3	12.4
n-Butane	2.14	2.76	2.65	2.99	3.16	3.13	2.01
1+2 Butenes	8.42	9.86	10.1	9.38	9.42	9.57	9.38
C ₄ Isomers	.871	.882	.831	1.01	1.07	1.18	1.05
n-Pentane	2.68	3.31	3.12	3.02	3.41	3.20	2.55
1+2 Pentenes	7.17	7.77	8.50	6.90	7.65	7.21	7.68
C ₅ Isomers	.498	1.02	.834	.762	.741	.722	.795
n-Hexane	2.03	1.93	1.94	1.90	1.44	2.01	1.69
1+2 Hexenes	6.06	4.81	5.35	4.42	3.89	5.26	4.57
C ₆ Isomers	1.38	1.03	1.11	.941	.802	1.30	1.11
n-Heptane	1.48	1.38	1.30	1.24	.983	1.50	1.21
1+2 Heptenes	3.80	2.82	3.15	2.00	1.88	2.98	2.79
C ₇ Isomers	.836	.630	.691	.507	.688	.921	1.07
n-Octane	.401	1.27	.896	1.14	.780	.881	.964
1+2 Octenes	.937	2.33	1.95	2.16	1.54	1.71	2.53
C ₈ Isomers	.223	.702	.455	.270	.588	.192	.980
n-Nonane	.312	1.17	.481	.831	.645	.539	.732
1+2 Nonenes	.782	1.97	1.02	1.48	1.30	1.25	2.00
C ₉ Isomers	.201	.541	.226	.378	.601	.510	.966
n-Decane	.471	1.07	.530	.551	.493	.571	.598
1+2 Decenes	1.07	1.55	1.07	.854	.874	1.35	1.47
C ₁₀ Isomers	.215	.518	.297	.198	.462	.436	.743
n-Undecane	.464	.763	.495	.420	.346	.506	.451
1+2 Undecenes	.972	.931	.857	.558	.527	1.12	1.01
C ₁₁ Isomers	.290	.388	.353	.124	.231	.327	.572
C ₂ -C ₄	42.4	43.4	42.2	44.8	43.6	44.5	37.2
C ₅ -C ₁₁	32.3	37.9	34.6	30.7	29.9	34.5	36.5
C ₁₂ +	12.0	2.39	5.75	5.89	10.5	5.70	13.4
Wax ^d	10.2	.259	.221	2.53	9.26	1.09	7.50

^d Unanalyzed wax collected from hot trap

Table 23. Comparison of runs FA-01-1547, FA-01-1807, and FA-01-0128 using United Catalyst' C-73 fused iron (170/230 mesh) at similar nominal conditions. (0.79 MPa, H₂/CO = 1).

Run	FA-01-1547	FA-01-1807	FA-01-0128	FA-01-1547	FA-01-0128
Period	1	1	6	2	2
Temperature (°C)	235				
Space Velocity (Nl/g-cat·h) ^a	0.75				
CO Conversion (%)	35.9	24.1	41.3	53.1	73.3
H ₂ +CO Conversion (%)	29.9	22.8	33.2	42.9	60.0
H ₂ /CO Usage	.64	.93	.69	.60	.72
STY (mols H ₂ +CO/g-cat·h) ^a	.020	.015	.022	.028	.039
1+2 Olefins/n-Paraffin Ratio					
C ₂	4.21	2.32	.95	1.83	.56
C ₃	5.76	4.92	3.43	6.17	4.44
C ₄	4.41	4.55	3.17	4.93	3.70
C ₈	3.73	4.12	2.36	2.96	1.88
C ₁₀	3.46	5.10	2.40	2.66	1.47
Weight % of Hydrocarbons					
CH ₄	9.2	3.51	15.3	6.4	16.3
C ₂ -C ₄	38.2	19.5	44.5	34.7	43.4
C ₅ -C ₁₁	39.9	48.9	34.5	35.3	37.9
C ₁₂ +	12.7	28.5	5.7	23.7	2.4
Wax ^b	7.0	2.15	1.1	17.6	.30

^a Based on unreduced catalyst

^b Unanalyzed wax collected from hot trap

Table 24. Summary of results for fixed bed run FA-15-0278.

Catalyst: 4.50 g^a, 100 Fe/1 Cu/0.2 K
Catalyst volume: 3.80 cc

Diluent: 35.8 g, Glass beads
Diluent Volume: 23.0 cc

Period	1	2	3	4	5
Date	1/29/88	1/30/88	1/31/88	2/01/88	2/02/88
Time on Stream (h)	48.8	72.0	97.0	120.8	145.0
Balance Duration (h)	6.0	6.0	6.0	6.0	6.0
Average Temperature (°C)	249.	234.	235.	220.	250.
Maximum Δ Temperature (°C) ^b	15.0	4.00	4.00	3.00	8.10
Pressure (MPa)	1.48	1.48	1.48	1.48	1.48
H ₂ /CO Feed Ratio	1.10	1.10	1.10	1.10	1.10
Space Velocity (NI/g-cat·h) ^a	2.00	2.00	4.00	2.00	2.00
Space Velocity (NI/g-Fe·h)	2.89	2.89	5.78	2.89	2.89
GHSV (h ⁻¹) ^c	333	333	667	333	333
CO Conversion (%)	87.1	45.2	27.1	23.9	67.2
H ₂ +CO Conversion (%)	76.6	44.7	26.2	24.2	58.9
H ₂ /CO Usage	.844	1.07	1.02	1.13	.838
STY (mols H ₂ +CO/g-cat·h) ^a	.068	.040	.047	.022	.053
$PCO_2 \cdot PH_2 / P_{CO} \cdot PH_2O$	10.8	1.24	1.08	.833	5.00
Weight % of Outlet					
H ₂	2.52	3.98	5.57	5.67	3.71
H ₂ O	5.93	8.81	5.33	5.10	5.61
CO	12.5	49.6	68.9	72.5	31.7
CO ₂	56.2	23.9	12.5	9.54	42.1
Hydrocarbons	18.9	10.3	5.47	3.61	12.8
Oxygenates	.443	.667	.267	.371	.436
Wax ^d	3.50	2.74	2.03	3.17	3.68
Yield (g/Nm ³ H ₂ + CO Converted)					
CH ₄	15.3	11.8	13.7	7.65	14.9
C ₂ -C ₄ Hydrocarbons	55.8	44.9	55.2	37.3	53.3
C ₆ -C ₁₁ Hydrocarbons	66.9	70.7	54.2	42.8	57.3
C ₁₂ + Hydrocarbons	41.6	63.9	57.8	87.2	46.8
Wax ^d	28.1	40.3	49.0	81.8	38.6
Oxygenates	3.55	9.80	6.45	9.59	4.57
Total	183.	201.	187.	185.	177.
1+2 Olefins/n-Paraffin Ratio					
C ₂	.502	1.10	.727	1.20	.635
C ₃	4.29	5.08	.35	5.27	4.10
C ₄	4.20	4.51	4.08	4.27	4.13
C ₈	1.93	2.28	2.36	2.81	1.96
C ₁₀	1.48	1.72	2.01	2.56	1.71

^a Based on unreduced catalyst

^c Based on reactor volume

^b Maximum axial temperature difference

^d Unanalyzed products collected from hot trap

Table 24 (cont'd). Summary of results for fixed bed run FA-15-0278.

Period		1	2	3	4	5
Weight % of Hydrocarbons						
C ₁₁ H ₄		8.53	6.15	7.56	4.37	8.67
Ethane		5.45	3.03	6.81	3.94	5.53
Ethylene		2.55	3.11	4.62	4.40	3.28
Propane		2.37	1.52	1.90	1.11	2.34
Propylene		9.71	7.36	7.88	5.57	9.14
n-Butane		1.99	1.46	1.75	1.14	1.97
i+2 Butenes		8.08	6.37	6.87	4.70	7.85
C ₄ Isomers		.904	.646	.698	.465	.844
n-Pentane		2.54	1.97	2.25	1.48	2.47
i+2 Pentenes		6.49	5.98	6.23	4.55	6.31
C ₅ Isomers		1.23	.675	.803	.344	1.09
n-Hexane		2.11	1.67	1.92	1.70	1.91
i+2 Hexenes		4.18	3.48	5.52	5.05	4.44
C ₆ Isomers		.747	.705	1.02	1.50	.780
n-Heptane		1.57	1.13	1.29	1.12	1.28
i+2 Heptenes		2.78	2.47	3.18	3.15	2.58
C ₇ Isomers		.662	.665	.680	.574	.520
n-Octane		1.42	1.21	.749	.544	1.07
i+2 Octenes		2.70	2.72	1.73	1.50	2.05
C ₈ Isomers		.508	.493	.456	.496	.338
n-Nonane		1.30	1.40	.317	.130	1.01
i+2 Nonenes		2.28	2.90	.664	.340	1.89
C ₉ Isomers		.599	.430	.106	.0504	.251
n-Decane		1.18	1.58	.443	.226	1.00
i+2 Decenes		1.71	2.68	.877	.572	1.69
C ₁₀ Isomers		.533	.599	.167	.0903	.272
n-Undecane		1.01	1.50	.480	.265	.827
i+2 Undecenes		1.25	2.10	.867	.632	1.23
C ₁₁ Isomers		.433	.626	.214	.117	.250
C ₂ -C ₄		31.1	23.5	30.5	21.3	30.9
C ₅ -C ₁₁		37.2	37.0	30.0	24.4	33.2
C ₁₂ +		23.2	33.4	32.0	49.9	27.1
Wax ^d		15.6	21.0	27.1	46.8	22.4

^d Unanalyzed wax collected from hot trap

Table 25. Analyzed compositions of the SiO₂ and Al₂O₃ supported catalysts.

Nominal Composition (parts by weight)	Analyzed Composition (parts by weight)
100 Fe/5 Cu/4.2 K/8 SiO ₂	100 Fe/5.1 Cu/4.0 K/7.8 SiO ₂
100 Fe/5 Cu/4.2 K/25 SiO ₂	100 Fe/5.4 Cu/4.6 K/28 SiO ₂
100 Fe/5 Cu/4.2 K/100 SiO ₂	100 Fe/5.3 Cu/4.1 K/96.5 SiO ₂
100 Fe/5 Cu/4.2 K/8 Al ₂ O ₃	100 Fe/5.0 Cu/3.9 K/7.7 SiO ₂
100 Fe/5 Cu/4.2 K/25 Al ₂ O ₃	100 Fe/5.1 Cu/4.0 K/20.5 SiO ₂
100 Fe/5 Cu/4.2 K/100 Al ₂ O ₃	100 Fe/4.7 Cu/4.2 K/31.6 SiO ₂

Figure 1. Example chromatogram of the RSL-150 wax analysis using conditions shown in Table 1.

Figure 2. Anderson-Schulz-Flory plot of the total product including analyzed wax from run FA-63-0418-5.

Figure 3. Schematic of the slurry reactor external slurry settling system.

Figure 4. Activity comparison (250 C, 1.48 MPa, H₂/CO = 1) of the SiO₂ supported catalysts with Ruhrchemie LP 33/81 and precipitated 100 Fe/3 Cu/0.2 K catalysts.

Figure 5. Stability plot of the CO reduction procedures.

Figure 6. Parity plot of the Fischer-Tropsch reaction kinetics.

Figure 7. Parity plot of the mass action water-gas shift reaction kinetics.

Figure 8. Parity plot for first order CO water-gas shift reaction kinetics.

Figure 9. TPR profiles in H₂ at 20 °C/min for calcined (16 h in air at 300 °C) samples of: (a) 100 Fe/5 Cu/8 SiO₂; (b) 100 Fe/5 Cu/25 SiO₂; (c) 100 Fe/5 Cu/100 SiO₂.

Figure 10. TPR profiles in H_2 at $20\text{ }^\circ\text{C}/\text{min}$ for calcined (16 h in air at $300\text{ }^\circ\text{C}$) samples of: (a) 100 Fe/5 Cu/4.5K/8 SiO_2 ; (b) 100 Fe/5 Cu/4.5K/25 SiO_2 ; (c) 100 Fe/5 Cu/4.5K/100 SiO_2 .

Figure 11. Isothermal reduction profiles in H₂ for calcined (16 h in air at 300 °C) samples of: (a) 100 Fe/5 Cu/8 SiO₂; (b) 100 Fe/5 Cu/25 SiO₂; (c) 100 Fe/5 Cu/100 SiO₂.

Figure 12. Isothermal reduction profiles in H_2 for calcined (16 h in air at 300 °C) samples of: (a) 100 Fe/5 Cu/4.2 K/8 SiO_2 ; (b) 100 Fe/5 Cu/4.2 K/25 SiO_2 ; (c) 100 Fe/5 Cu/4.2 K/100 SiO_2 .

Figure 13. TPR profiles in H_2 at $20\text{ }^\circ\text{C}/\text{min}$ for calcined (16 h in air at $300\text{ }^\circ\text{C}$) samples of: (a) 100 Fe/5 Cu/8 Al_2O_3 ; (b) 100 Fe/5 Cu/25 Al_2O_3 .

Figure 14. TPR profiles in H_2 at $20\text{ }^\circ\text{C}/\text{min}$ for calcined (16 h in air at $300\text{ }^\circ\text{C}$) samples of: (a) 100 Fe/5 Cu/4.2 K/8 Al_2O_3 ; (b) 100 Fe/5 Cu/4.2 K/25 Al_2O_3 .

Figure 15. Isothermal reduction profiles in H_2 for calcined (16 h in air at $300^\circ C$) samples of: (a) 100 Fe/5 Cu/ 8 Al_2O_3 ; (b) 100 Fe/5 Cu/25 Al_2O_3 .

Figure 16. Isothermal reduction profiles in H_2 for calcined (16 h in air at 300 °C) samples of: (a) 100 Fe/5 Cu/4.2 K/8 Al_2O_3 ; (b) 100 Fe/5 Cu/4.2 K/25 Al_2O_3 .

Figure 17. XPS spectra of 100 Fe/5 Cu/4.2 K/8 SiO₂ in Fe 2p region. (a) following exposure to H₂ at 300 °C; (b) following subsequent exposure to H₂/CO at 250 °C.

Figure 18. XPS spectra of 100 Fe/5 Cu/4.2 K/8 SiO_2 in O 1s region. (a) following exposure to H_2 at 300 °C; (b) following subsequent exposure to H_2/CO at 250 °C.

Figure 19. XPS spectra of 100 Fe/5 Cu/4.2 K/8 SiO₂ in K 2p and C 1s regions. (a) following exposure to H₂ at 300 °C; (b) following subsequent exposure to H₂/CO at 250 °C.

Figure 20. XPS spectra of 100 Fe/5 Cu/4.2 K/8 SiO_2 in Fe 2p region. (a) following exposure to CO at 300 °C; (b) following subsequent exposure to H_2/CO at 250 °C.

Figure 21. XPS spectra of 100 Fe/5 Cu/4.2 K/8 SiO₂ in K 2p and C 1s regions. (a) following exposure to CO at 300 °C; (b) following subsequent exposure to H₂/CO at 250 °C.

Figure 22. XPS spectra of 100 Fe/5 Cu/4.2 K/8 Al₂O₃ in Fe 2p region. (a) following exposure to H₂ at 300 °C; (b) following subsequent exposure to H₂/CO at 250 °C.

Figure 23. XPS spectra of 100 Fe/5 Cu/4.2 K/8 Al₂O₃ in K 2p and C 1s regions. (a) following exposure to H₂ at 300 °C; (b) following subsequent exposure to H₂/CO at 250 °C.

Figure 24. XPS spectra of 100 Fe/5 Cu/4.2 K/8 Al₂O₃ in Fe 2p region. (a) following exposure to CO at 300 °C; (b) following subsequent exposure to H₂/CO at 250 °C.

Figure 25. XPS spectra of 100 Fe/5 Cu/4.2 K/8 Al₂O₃ in K 2p and C 1s regions. (a) following exposure to CO at 300 °C; (b) following subsequent exposure to H₂/CO at 250 °C.

TEXAS A&M UNIVERSITY

Figure 26. XPS spectra of 100 Fe/5 Cu/4.2 K/25 SiO₂ in Fe 2p region. (a) following exposure to H₂ at 300 °C; (b) following subsequent exposure to H₂/CO at 250 °C.

Figure 27. XPS spectra of 100 Fe/5 Cu/4.2 K/25 SiO₂ in K 2p and C 1s regions. (a) following exposure to H₂ at 300 °C; (b) following subsequent exposure to H₂/CO at 250 °C.

Figure 28. XPS spectra of 100 Fe/5 Cu/4.2 K/25 SiO₂ in Fe 2p region. (a) following exposure to CO at 300 °C; (b) following subsequent exposure to H₂/CO at 250 °C.

Figure 29. XPS spectra of 100 Fe/5 Cu/4.2 K/25 SiO₂ in K 2p and C 1s regions. (a) following exposure to CO at 300 °C; (b) following subsequent exposure to H₂/CO at 250 °C.

Figure 30. XPS spectrum in Fe 2p region of 25 weight % Fe/SiO₂ following exposure to O₂ at 300 °C and subsequent cooling in O₂ to 25 °C.

Sample Description: IRON OX. IN VAC.

TEXAS A&M UNIVERSITY

Figure 31. XPS spectrum in Fe 2p region of 25 weight % Fe/SiO₂ following exposure to O₂ at 300 °C, subsequent evacuation at 300 °C, and cooling in vacuum to 25 °C.

Sample Description: RED.500C IN H₂

Figure 32. XPS spectrum in Fe 2p region of 25 weight % Fe/SiO₂ following exposure to H₂ at 500 °C.

Sample Description: RED.300 IN H2

Figure 33. XPS spectrum in Fe 2p region of 25 weight % Fe/SiO₂ containing 1 weight % Cu following exposure to H₂ at 300 °C.

Sample Description: RED.300 IN H2

Figure 34. XPS spectrum in Cu 2p region of 25 weight % Fe/SiO₂ containing 1 weight % Cu following exposure to H₂ at 300 °C.

Sample Description: IRON RED. IN SYN-GAS

TEXAS A&M UNIVERSITY

Figure 35. XPS spectrum in Fe 2p region of 25 weight % Fe/SiO₂ containing 1 weight % Cu following exposure to H₂/CO at 300 °C.

Figure 36. TPR profile in H_2 at $20\text{ }^\circ\text{C}/\text{min}$ for a calcined (16 h in air at $300\text{ }^\circ\text{C}$) sample of 25 weight % Fe/ SiO_2 .

Figure 37. TPR profile in H_2 at $20\text{ }^\circ\text{C}/\text{min}$ for a calcined (16 h in air at $300\text{ }^\circ\text{C}$) sample of 25 weight % Fe/SiO_2 containing 0.1 weight % Cu.

Figure 38. TPR profile in H_2 at $20\text{ }^\circ\text{C}/\text{min}$ for a calcined (16 h in air at $300\text{ }^\circ\text{C}$) sample of 25 weight...
% Fe/ SiO_2 containing 1 weight % Cu.

Figure 39. TPR profile in H_2 at $20^\circ\text{C}/\text{min}$ for a calcined (16 h in air at 300°C) sample of 25 weight % Fe/SiO_2 containing 3 weight % Cu .

Figure 40. TPR profile in H_2 at $20\text{ }^\circ\text{C}/\text{min}$ for a calcined (16 h in air at $300\text{ }^\circ\text{C}$) sample of 25 weight % Fe/ SiO_2 , following prior exposure to H_2 for 16 h at $300\text{ }^\circ\text{C}$.

Figure 41. TPR profile in H_2 at $20\text{ }^\circ\text{C}/\text{min}$ for a calcined (16 h in air at $300\text{ }^\circ\text{C}$) sample of 25 weight % Fe/ SiO_2 containing 1 weight % Cu, following prior exposure to H_2 for 16 h at $300\text{ }^\circ\text{C}$.

Figure 42. TPR profile in H_2 at $20\text{ }^\circ\text{C}/\text{min}$ for a calcined (16 h in air at $300\text{ }^\circ\text{C}$) sample of 25 weight % Fe/ SiO_2 , following prior exposure to H_2 for 16 h at $500\text{ }^\circ\text{C}$.

Figure 43. Infrared spectrum of unpromoted iron precipitate following exposure to O₂ at 300 °C, evacuation at 300 °C, and subsequent exposure to gaseous NO at 25 °C.

Figure 44. Infrared spectrum of unpromoted iron precipitate following exposure to O₂ at 300 °C, evacuation at 300 °C, exposure to H₂/CO at 300 °C, and subsequent exposure to gaseous NO at 25 °C.

APPENDIX I

Summary of Catalyst Synthesis and Drying Procedure

(a). Iron/Copper Co-Precipitation Procedure.

Desired compositions of copper-promoted iron-based catalysts are prepared by a continuous co-precipitation technique. An aqueous solution containing $\text{Fe}(\text{NO}_3)_3$, together with a concentration of $\text{Cu}(\text{NO}_3)_2$ that corresponds to the desired Fe/Cu ratio in the final catalyst, and a second solution containing aqueous NH_3 are maintained in heated stirred glass vessels. The two solutions are separately conveyed by fluid pumps to a stirred tubular reaction vessel which is also heated. Precipitation (to form $\text{FeOOH}/\text{Fe}_2\text{O}_3$ and $\text{Cu}(\text{OH})_2$) occurs continuously as the two solutions are pumped upward through the vessel, while an in-line pH electrode is used to monitor the pH of the reactor effluent. The flow rate of the NH_3 solution is normally fixed, while that of the $\text{Fe}^{3+}/\text{Cu}^{2+}$ solution is adjusted to give the desired precipitation pH. Collection of the slurried precipitate is made in ice-cooled vessels and is continued until one of the two solutions is consumed. The precipitate is then thoroughly washed by vacuum filtration to remove excess NH_3 and NO_3^- using deionized, distilled water. If the catalyst will contain no silica binder, the washed precipitate is then dried. Drying of silica-containing catalysts is performed after impregnation of the precipitate with potassium silicate (*vide infra*).

(b). Binder Incorporation Procedure.

Impregnation with SiO_2 binder/support is accomplished by re-slurrying moist, undried precipitate in water, followed by addition of an appropriate amount of a dilute K_2SiO_3 solution to produce a material having the desired Fe/Cu/ SiO_2 composition. Solution pH after K_2SiO_3 is adjusted to ensure complete decomposition of K_2SiO_3 (with its accompanying deposition of SiO_2) on the $\text{FeOOH}/\text{Fe}_2\text{O}_3/\text{Cu}(\text{OH})_2$ precipitate and to prevent loss of copper and/or iron by dissolution. The resulting silica-containing slurry is stirred to ensure complete penetration of SiO_2 (i.e., K_2SiO_3 solution) into the precipitate pores. Catalyst synthesis is completed by subsequent washing, filtration, and vacuum drying.

Incorporation of Al_2O_3 binder/support is performed using an Fe/Cu precipitate of the desired composition that has already been dried. Under an atmosphere of dry nitrogen (to prevent exposure to atmospheric water), an appropriate amount of liquid aluminum *sec*-butoxide is dissolved in a volume of 2-butanol needed to just fill the pores of the precipitate sample and achieve "incipient wetness". The required amount of dried Fe/Cu precipitate is added to the butoxide solution, and the resulting slurry is stirred to ensure complete pore filling by the viscous alkoxide solution. Hydrolytic decomposition of the impregnated aluminum *sec*-butoxide to form Al_2O_3 is accomplished by exposure of the material to air that is saturated with water vapor. The final alumina-containing catalyst is then thoroughly washed and re-dried.

(c). Potassium Impregnation Procedure.

Addition of the desired levels of potassium promoter to all precipitated Fe/Cu catalysts, with or without silica or alumina binder, is performed by a pore-filling technique using dried precipitate. In this method, the required amount of KHCO_3 is dissolved in water. The solution is then added to a weighed sample of catalyst, resulting in the so-called "incipient wetness" condition. This procedure ensures uniform and complete distribution of the potassium salt throughout the catalyst pore structure. Excess solvent is then removed by vacuum-aided evaporation, with continuous rotational agitation. The final product is dried further in a vacuum oven.

END

**DATE
FILMED**

8/21/92