THE EFFECTS OF RADIOLYSIS ON THE CORROSION AND STRESS CORROSION BEHAVIOR OF 316 STAINLESS STEELS

D.J. Duquette and D. Steiner

Rensselaer Polytechnic Institute, Troy, New York 12180

SUMMARY

This program is focused on the corrosion, stress corrosion and corrosion fatigue behavior of Type 316 stainless steel (316SS) at 50, 90, and 130°C in high-purity water. Irradiated solution tests are performed using high-energy photon radiation. The purpose of this work is to determine the effects of radiolysis products on the environmental stability of 316SS in support of the ITER first wall/shield/blanket design. Preliminary results suggest that irradiation of pure water at 50°C results in a shift in the electrochemical potential of 316SS of approximately 100mV in the active direction and nearly an order of magnitude increase in the passive current density as compared to non-irradiated conditions. This proposal outlines a three-year program to develop corrosion design criteria for the use of 316SS in an ITER environment.

HISTORICAL BACKGROUND AND MOTIVATION

The International Thermonuclear Energy Reactor (ITER) currently utilizes water as the coolant for the first wall, shield and driver blanket components. Type 316 austenitic stainless steel (316SS) has been selected as the structural material for these components.

MASTER

DM 1
DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

The ITER coolant and structural material will be subjected to an intense radiation field (neutrons and photons). According to Allen[1] and Pikaev[2], irradiation of water produces primary and secondary radiolysis products including: e^-_{aq} , H, H_2 , OH, H_2O_2 , HO $_2$, O_2 , O_2^- , H^+ , and OH $^-$. Of these, e^-_{aq} , H, H_2 , and HO $_2$ are reducing species, while OH, H_2O_2 , O_2 , O_2^- are oxidizing species. Marsh et al.[3] noted that these species generally balance each other in a closed, single phase system so that there is no net oxidizing or reducing effect. However, if the system is open to a gas space where gaseous species can escape, a net oxidizing or reducing environment can be produced depending on the gas composition. The oxidizing or reducing power of the solution environment will have a marked effect on the potential of a metal or alloy exposed to the solution.

Several investigators have observed noble shifts of the potentials of Type 304 and 304L stainless steels under gamma irradiation of aqueous solutions[3-6]. In tests simulating boiling water reactor (BWR) environments, Saito et al.[6] reported a noble shift in the potential of 304SS under normal water chemistry (NWC) conditions. This observation was attributed to the resulting oxidizing radiolysis environment. An active potential shift was observed under hydrogen water chemistry (HWC) conditions, which the authors attributed to a net reducing environment. NWC conditions are characterized by a dissolved oxygen concentration (DO) of approximately 200 ppb compared to HWC with DO of approximately 15 ppb[6]. Hydrogen gas

ultimately acts as an oxygen scavenger. These shifts in corrosion potential can result in either increases or decreases in the general corrosion rates of stainless steels from that observed in un-irradiated solutions.

It has also been postulated that Fe-Ni-Cr alloys may become susceptible to accelerated stress corrosion cracking (SCC) if the potential lies in or above potential ranges of passive film kinetic instability (at the active-passive transition and transpassive ranges)[7]. Conditions which may shift the potential into the critical potential ranges include oxidizing species (e.g. H_2O_2 , O_2 , O_2^-), specific ions (e.g. Cl^- , F^-), and conditions such as galvanic coupling or crevice effects which may locally polarize the alloy. The existence of critical ranges for SCC susceptibility is a fundamental consideration in the slip-dissolution model for SCC, which is applicable to both transgranular and intergranular stress corrosion cracking (IGSCC).

A principal concern in ITER water-cooled components is that radiolysis products will shift the electrochemical potential of 316SS into a range of increased SCC susceptibility. Moreover, the ITER components will be welded structures, using solution annealed 316SS. Thermal sensitization in the structural welds is possible. Additionally, accumulated damage from the high-energy neutron flux may lead to radiation-induced sensitization and solute segregation in the stainless steel. Inazumi et al.[8] investigated radiation-induced sensitization at temperatures of

interest to ITER. According to Staehle[7], "the intergranular SCC of stainless steels depends critically on some combination of sensitization, grain boundary segregation, applied stress, dissolved oxygen, other environmental contaminants, and temperature." Recent studies[6,9,10] of 304SS and 316SS in fission reactor environments have shown that the alloys are the most susceptible to IGSCC in the sensitized condition with appreciable dissolved O_2 in solution. In view of the complex nature of IGSCC, it is important to study the SCC susceptibility of sensitized and solution annealed 316SS under conditions relevant to ITER, with the electrochemical potential fixed in the critical ranges for SCC susceptibility.

In addition to the SCC considerations, the oxidizing or reducing radiolysis products may enhance the corrosion rate of 316SS. This is particularly undesirable if the general corrosion losses exceed the allowable limits for the design lifetime of the fusion reactor. From the health physics viewpoint, increased corrosion rates result in higher activated corrosion product (crud) levels in coolant passages. Recent work[11,12] on 316SS and 304SS under conditions of solution irradiation has shown that the corrosion product release is dependent on the electrochemical potential.

Still another consideration is the role of the environment, and radiolytically induced shifts in electrochemical potentials, on the fatigue resistance of 316 stainless steel. It can be anticipated that a fusion reactor will be subjected to vibratory

loads (high cycle fatigue) and lower frequency thermally induced fluctuating loads, which may induce corrosion fatigue (CF) crack initiation and growth.

PROGRESS TO DATE

The conditions relevant to the ITER coolant blanket are neutral, high purity water at 50, 90 and 130°C. If electrochemical potential shifts due to irradiation result in corrosion and/or stress corrosion cracking enhancement, it may be possible to adopt the hydrogen water chemistry schemes currently being utilized to control IGSCC in boiling water reactors[13].

The work to date has been directed at developing a database of electrochemical measurements on 316SS in non-irradiated and irradiated high purity water at 25, 50, 90, and 130°C. The water is deaerated with hydrogen gas (H_2). The dissolved hydrogen concentration (DH) is approximately 1500 ppb at 50°C. In order to obtain solution conductivity required for electrochemical measurements, 0.0005 mole/liter potassium sulfate (K_2SO_4) is added to the high purity water. Laboratory results obtained in this program, at Rensselaer, have shown that this concentration of K_2SO_4 does not affect the corrosion behavior of 316SS in deaerated solutions.

Electrochemical measurements are being performed in irradiated solutions at the RPI linear electron accelerator (LINAC). Laboratory simulation of the irradiated conditions is underway, using a radiolysis code[14] to approximate the chemistries produced by irradiation of the water. These

simulated solutions will be used in SCC and CF tests.

SCC susceptibility is being tested using the slow strain rate technique (SSRT) at fixed potentials. The probable critical potential ranges for SCC susceptibility are being determined from the electrochemical data.

CF resistance, with particular reference to crack initiation is being evaluated utilizing a closed-loop test system (crack propagation tests are being performed at the Argonne National Laboratory (ANL)). As with the SCC tests, the critical variables will be solution test temperature and solution chemistry.

APPARATUS

The corrosion test apparatus to be used in this test program consists of a conventional, 2 liter solution volume, electrochemical cell. The electrochemical data are generated through potentiodynamic polarization scans and open circuit potential versus time tests, utilizing automated potentiostats.

The LINAC high-energy electron beam, striking a tantalum target, produces photons via the Bremsstrahlung process. The electrochemical cell is subjected to gamma energies of 60 MeV maximum and 20 MeV average. The average dose rate is 340 krad/hour.

The radiolysis code was developed by Khalak[14] for fusion reactor applications. This code has been used in recent work[10] to model radiolysis product yields for SCC testing.

Slow strain rate experiments are being performed on a constant extension rate tensile testing machine. Strain rates of

10^{-8} to 10^{-3} s^{-1} are possible. An environment cell has been constructed which will allow the potential to be potentiostatically fixed during the SSRT experiments.

Corrosion fatigue tests will be performed on a conventional fatigue test apparatus, with frequency capability from 0.01 - 20 Hz. The loading pattern will be in tension-tension with a triangular wave form. An environment cell with fixed potential capability is being designed.

RESULTS TO DATE

Upon irradiating the electrochemical cell at 50°C , the electrochemical potential of 316SS is shifted by approximately 100mV in the active direction. This shift was observed in open circuit potential versus time tests and in potentiodynamic polarization scans. The potential shift can be seen by comparing the zero-current potentials of the potentiodynamic polarization scans shown in Figures 1 and 2. Reduction/oxidation (redox) measurements on inert platinum show the same potential shift and indicate that it is driven by the radiolysis products in the solution.

Potentiodynamic polarization scans in 50°C , irradiated solutions show nearly an order of magnitude increase in the passive current density of 316SS compared to that observed under non-irradiated conditions. This difference is noted in the passive regions of the potentiodynamic polarization scans (-0.200V to -0.400V vs. SSE) shown in Figures 1 and 2. Potentiodynamic polarization data for redox reactions on inert

platinum in the irradiated solution do not show a proportionate increase in current density.

DISCUSSION

In the present experiments, hydrogen gas is continuously introduced into the irradiated electrochemical cell, and gaseous radiolysis products are carried away. Marsh et al.[3] has noted that the composition of the cover gas is critical to the net yield of radiolysis products. With hydrogen cover gas, high concentrations of H_2 and H will persist in the solution and preclude the build up of oxidizing species. An excess of reducing radiolysis products (e^-_{aq} , H , HO_2) is formed, leading to a net reducing environment. The observed active potential shifts on 316SS can be attributed to a reducing environment produced via radiolysis. This conclusion is consistent with Saito et al.[6], for 304SS under HWC conditions, which showed a negative, or active, shift in the open circuit potential of stainless steel. Table I compares the experimental conditions of the present work to that of Saito et al.[6].

Table I. Comparison of experimental conditions for stainless steels under gamma irradiation.

Alloy	Temperature, °C	DH, ppb	Dose rate, krad/hr
316SS (present work)	50	1500	340
304SS (ref[6])	270	100	140

The increase in passive current density with irradiation of

the aqueous solution for 316SS can be attributed to either: 1) an increase in the passive corrosion rate of the alloy; or 2) an increase in redox reaction rates on the alloy surface. If surface redox reactions are the cause, then one would expect a proportionate increase in current density with irradiation on inert platinum. Comparing the data for 316SS and platinum, preliminary indications are that the increased current density can be attributed to increased passive corrosion rates in the irradiated solution. Corrosion rates calculated from the minimum current densities of the polarization curves are shown in Table II. One should note that corrosion rates taken from a potentiodynamic polarization curve are "instantaneous" rates which do not account for the protection the passive oxide film provides once it has formed, and probably reflect a "worst case" situation.

Ishikawa et al.[11] also have studied corrosion of 316SS and 304SS in a gamma radiation field. The authors verified the results of Hirayama et al.[12], showing that the corrosion product release is dependent on the corrosion potential. Under NWC (higher DO, low DH) the irradiated environment becomes more oxidizing, shifting the potential towards the transpassive region. Chromium complexes ($\text{Cr}_2\text{O}_7^{2-}$, CrO_4^{2-}) are more soluble in the oxidizing environment, resulting in dissolution of chromium oxide (Cr_2O_3) from the passive film. For iron, the ferrous (Fe^{2+}) ion is oxidized to ferric (Fe^{3+}) ion, which deposits on the outer layer of the passive film. The Fe^{3+} ion is not dissolved due to

its low solubility in the low DH (oxidizing) environment.

Under HWC (low DO, higher DH) the irradiated environment is reducing, with a corresponding negative shift in the electrochemical potential. This environment provides increased solubility of iron, nickel, and cobalt ions. The authors point out that these ions are readily transported through the oxide film and released into solution because the low oxygen concentrations are insufficient to maintain the film. Chromium is not readily dissolved due to its low solubility in the low DO (reducing) environment and it becomes concentrated in the oxide film. Accordingly, under conditions relevant to ITER, the specification of water chemistry may control the composition of passive films as well as determine the soluble and insoluble species in the aqueous solutions. While the present program is concentrating on HWC, future experiments also will examine NWC conditions.

Table II. Calculated passive corrosion rates for 316SS, 50°C, 0.0005M K₂SO₄, deaerated with H₂

Environment	Corrosion rate (μm/yr)
Non-irradiated	5.8
Irradiated	43

PRELIMINARY CONCLUSIONS

Irradiation of 316SS at 50°C in an environment relevant to the ITER water-cooled components results in the following observations:

- (1) A shift in the electrochemical potential of approximately 100mV in the active direction. This shift is attributed to the formation of a net reducing environment via radiolysis.
- (2) Nearly an order of magnitude increase in the passive corrosion rate as compared to non-irradiated conditions. Further testing on 316SS and platinum is required to confirm this hypothesis.

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

END

**DATE
FILMED**

7 / 22 / 92