Quarterly Technical Progress Report No. 8
For Period
November 1, 1989 through January 31, 1990

SURFACE MAGNETIC ENHANCEMENT FOR COAL CLEANING

Submitted to:

U.S. Department of Energy
Pittsburgh Energy Technology Center
P.O. Box 10940
Pittsburgh, PA 15236

Contract Number: DE-AC22-88PC88856

Technical Program Officer: McMahan L. Gray

Prepared by:

Project Manager and Principal Investigator

J. Y. Hwang
Program Manager - Minerals

Institute of Materials Processing
Michigan Technological University
Houghton, Michigan 49931

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

MASTER

SUMMARY AND FUTURE WORK

The fundamental chemistry for selective adsorption of magnetizing reagent on coal-associated minerals to enhance the magnetic susceptibilities of minerals have been established in Phase I study. The application of the results on coal cleaning is in progress in the Phase II study. Illinois No. 6, Ohio Lower Kittanning, and West Virginia Pocahontas coals are investigated during this reporting period to determine the most effective way of using the magnetizing method for coal cleaning. The results show that the best separation performance is obtained on finely ground coals. Up to 91% ash reduction (from 22% to 3.3% ash content) at 70% coal recovery can be obtained with the magnetizing approach when Illinois No. 6 coal is processed at 90% passing 500 mesh. Even at a coarser sizes such as 90% passing 200 mesh, 86% ash reduction with 71% coal recovery can still be obtained. Although the results are probably better than using the froth flotation method, direct comparison tests will be conducted in the next reporting period.

In the next quarter, Phase II will be completed and Phase III will be started.

INTRODUCTION

This research studies the surface enhancement of magnetic susceptibility of minerals for coal cleaning. The enhancement is achieved by adsorbing magnetizing reagent on minerals. The objectives of the study include: (i) to define the optimal conditions for adsorption selectivity and magnetic enhancement using magnetizing reagent approach, (ii) to determine the effect of such magnetic enhancement on the coal cleaning efficiency with magnetic separations, and (iii) to evaluate where this method can be adapted to the existing coal processing schemes for maximum effectiveness.

Three phases of work are included in this research: a fundamental study, an application study, and an industrial laboratory study. The fundamental study investigates the basic chemistry involved in the interactions of magnetizing reagents and minerals. The application study employs the basic chemistry for coal cleaning under various process schemes. The work performed during this reporting period is part of the application study. Major efforts are on the process adaptation testing (Task 8).

PROGRESS BY WORK BREAKDOWN STRUCTURE

Task 1. Magnetizing Reagent Preparation

Thirty five magnetizing reagents with various surfactant functional groups have been prepared for this study. The properties of these reagents were documented in the previous reports. Five reagents, selected from different cationic, anionic, and nonionic categories, were investigated for

their shelf life. The results show that magnetizing reagents are stable for long term storage. This task is completed.

Task 2. Mineral/Reagent Interactions

The interactions of magnetizing reagents and minerals under various conditions have been investigated. The conditions include pH, kinds and dosages of magnetizing reagents, mineral activator, coal depressant, oxidation effect, and slurry regulators. All of the experimental results have been described in the previous reports. This task is completed.

Task 3. Magnetite Size Effect

The particle size of magnetite and its effects on the properties of magnetizing reagents were studied. The experiments show that smaller magnetite particles provide better metallurgical results. This task is completed.

Task 4. Phase I Data Evaluation

All of the results in Phase I study have been evaluated. The most promising conditions for selective magnetic enhancement of coal-associated minerals have been selected.

Task 5. Phase I Report and Review

The reports documenting the progress in Phase I study have been completed and reviewed.

Task 6. Coal Selection, Preparation, and Characterization

Three coals are selected for the Phase II study. They are Illinois No. 6, Ohio Lower Kittanning, and West Virginia Pocahontas No. 3 seams. Each 400 pound sample was prepared simulating the commercial operations to yield the feed for this study. The circuits include heavy media, tabling, and froth flotation separations. Characterization study includes coal analysis, grindability, washability, mineralogy, and maceral and pyrite

distributions. The results were described in the previous reports. This task is completed.

Task 7. Optimization of Magnetizing Conditions

Eleven promising conditions to yield selective adsorption of magnetizing reagent on coal-associated minerals have been evaluated on the basis of magnetic separations. The three coals at -48 mesh prepared in Task 6 were utilized in these tests. The results show that enhanced separation is particularly successful with an approach which uses a hydrophillic modifier for coal depressing and a cationic magnetizing reagent for mineral magnetic enhancement. A reduction of 92% ash and 83% pyrite can be achieved. In addition, flotation concentrates of these coals at -48 mesh were also examined with this approach. The results show that the magnetic enhancement approach performs better than the recleaning flotation approach. At the same extent of pyrite reduction, the magnetic enhancement approach gains 12% additional coal yield than the recleaning flotation approach does for Illinois No. 6 coal. The better selectivity on removing the unliberated pyrite from coal particles is believed the reason. This task is completed.

Task 8. Process Adaptation Testing

This task is to determine the best way to adopt the magnetizing method to the existing coal preparation and utilization scenarios. Three options are included. The first option is to condition the coal concentrates with the magnetizing reagent at the preparation plant, dry pulverize the coal at power plant, and conduct dry magnetic separation before combustion. The second option is to process the preparation plant middlings. The third option is in the area of fine coal cleaning.

Experimental results show that the third option yields best separation performance. Up to 91% ash rejection can be obtained with this option. The

ash content versus coal recovery curves at various grinding are shown in Figure 1 and 2 for the ROM coals of Illinois No. 6 and Lower Kittanning. The first option has the difficulties on dry magnetic separation, although wet magnetic separation can be successful. Wet magnetic separation is not favored in the first option because of economic reasons. The second option study indicates that the liberation of minerals in the middlings is a problem. The processing of the middlings will require very fine grinding. The details of the experiments are described below.

Option 1.1. Table Concentrate Processing. In the last report, it was shown that magnetizing reagent conditioned table concentrate had selective magnetic enhancement on the minerals fraction. Pulverizing did not smear the magnetite away from mineral surface. Wet magnetic separation of the reagent conditioned and dry pulverized coal could reduce the ash and pyrite contents significantly. During this reporting period, dry magnetic separation tests of the reagent conditioned and pulverized coal have been conducted. The reagent dosages are 0.96 lb/ton hydrophillic modifier and 0.48/lb magnetizing reagent. Steel wool is the separator matrix. Powders of coal were passing upwards through the matrix using a vacuum machine. The results are shown in Table 1, 2, and 3 for the three coals, respectively. Very small amounts of ash reduction are achieved. The variation of magnetic field strength shows no effects. Therefore, the dry separation is regarded inadequate for this option.

Option 1.2. Heavy Media Concentrate Processing. Heavy media concentrates of the three coals were processed using the same methods as described for the processing of table concentrates, except changing the dosages of hydrophillic modifier and magnetizing reagent to 0.25 lb/ton and 0.125 lb/ton, respectively. The results of wet magnetic separation were demonstrated in the last report, which showed a slight reduction of ash

content. The dry magnetic separations were conducted in this period. The results are shown in Table 4, 5, and 6. Small amounts of ash reduction are observed only at 20 kilogauss. No reduction can be confirmed at lower magnetic field strength. The incapability of dry magnetic separation for this process is obvious.

Option 1.3. Flotation Concentrate Processing. Flotation concentrate prepared in Task 6 was conditioned with 10 lb/ton hydrophillic modifier and 5 lb/ton magnetizing reagent. The conditioned coal was filtered, dried, and pulverized to 80% passing 200 mesh. Dry magnetic separations at various magnetic field strengths were conducted subsequently. The results of separation for the three coals are shown in Table 7, 8, and 9. The extent of ash reduction is still not satisfactory. For example, the ash content is reduced from 10.50% to 8.59% for Illinois No. 6. This ash content is much higher than the 4.21% achieved with the wet magnetic separation on the flotation concentrate (Table 6 in Report No. 7). However, this reduction is already a significant improvement comparing the dry magnetic separations of table and heavy media concentrates.

Option 2. Heavy Media Middlings Processing. Heavy media middlings with specific gravities between 1.3 and 2.0 were prepared in Task 6. The middlings were crushed to minus 48 mesh and then conditioned with reagents. The dosages of reagents are 20 lb/ton for the hydrophillic modifier and 10 lb/ton for magnetizing reagent. Magnetic separation of the slurry include a run at 18 kilogauss and 18 cm/sec slurry velocity with a grooved plate matrix and three runs at 5 kilogauss and 5.7 cm/sec slurry velocity with a screen matrix. The magnetics from the grooved plate run are the reject. The nonmagnetics after the screen runs are the concentrate. The magnetics obtained from the screen runs are the middlings. The middlings were ground to 200 mesh and reconditioned with the same amounts of

hydrophillic modifier and magnetizing reagent as described above. Magnetic separation was conducted at 18 kilogauss with steel wool matrix for three times. Slurry velocity was free falling. The results are shown in Table 10, 11 and 12 for the three coals. The ash content in the concentrate of this approach is higher than that obtained from ROM coal at the same size. For example, the ash contents of ROM coals at -48 mesh can be cleaned to 6.50%, 2.26%, and 4.93% for Illinois No. 6, Lower Kittanning, and Pocahontas, respectively (see Tables 3, 4, and 5 of Report No. 7). For the heavy media middlings of the three coals, the ash contents using the same magnetizing approach can only achieve 11.08%, 3.94%, and 12.37%. The cleaning of magnetic middlings is even more difficult, as demonstrated by the poor separation in the Tables. The poor liberation of the middlings is believed to be the reason.

Option 3.1. Fine Coal Processing for Illinois No. 6. The ROM coal of Illinois No. 6 was wet ground to various sizes with tap water. Four sizes were included in the tests. They are 90% passing of 500, 325, 200, and 100 meshes, respectively. Each ground coal was conditioned with hydrophillic modifier and magnetizing reagent at various dosages. Magnetic separation of the conditioner was conducted at various field strengths. The coarse steel wool was utilized as the matrix. Slurry was gravitationally fed through the separator without velocity control (near free falling velocity). Repeated separations were utilized to obtain various retention times of separation.

Separation results for the 90% passing 500 mesh at various magnetic field strengths are shown in Table 13. Ash reduction increases with magnetic field strengths from 2 to 10 kilogauss. From 10 to 20 kilogauss, the separation results are almost identical. Ash content can be reduced from about 22% to 3.3% for the Illinois No. 6 coal. Pyritic sulfur analysis

will be reported in the next report. Ash reduction is about 91%. Coal yield is about 57% (about 70% recovery of coal). The effect of reagent dosages on the separations is shown in Table 14. The optimum dosage is obviously at 20 lb/ton magnetizing reagent (on the basis of magnetite).

Table 15 shows the reagent dosage effect on the processing of 90% passing 325 mesh coal at 18 kilogauss. The ash content can be reduced from 21% to 3.6% with about 52% yield (63% coal recovery). Table 16 shows the results using various magnetic field strengths. A magnetic field strength at about 10 kilogauss is sufficient for the separation.

For the coal ground to 90% passing 200 mesh, the effect of reagent dosage is demonstrated in Table 17. Ash can be reduced to 4.2% with about 59% yield. The magnetic field strength for the separation at the 200 mesh size requires about 15 kilogauss, as shown in Table 18. This strength requirement is higher than that for the 325 and 500 mesh materials.

Tests on the 90% passing 100 mesh coal have only been studied with the effect of reagent dosage. The results are reported in Table 19. The ash content can still be reduced to 4.2%. However, the yield is low. The mechanical entrainment of coarse particles in the wool matrix and the liberation may both cause the low yield.

A comparison on the optimum separations at different particle sizes can be obtained from Figure 1. It is obvious that the separation efficiency increases with the grinding. The improvement of liberation with grinding is the major reason. The increase of surface area ratio with the decrease of particle size may be another reason because fine particles may obtain higher magnetic enhancement through the adsorption of magnetizing reagent than the coarse particles.

Option 3.2. Fine Coal Processing for Lower Kittanning. The procedures for processing Lower Kittanning coal at fine particle sizes are the same as

that for processing the Illinois No. 6 coal. The test matrix includes the four different particle sizes. For the study on each particle size, reagent dosage and magnetic field strength are varied to determine their effects on separation.

The results for processing at 90% passing 500 mesh are shown in Table 20 by varying the reagent dosage. It is obvious that the best separation occurs at about 10 lb/ton magnetizing reagent dosage. This dosage is much less than that for the Illinois No. 6 coal. The reason is probably that Lower Kittanning coal is much more hydrophobic, which subsequently yield stronger adsorption of the hydrophillic modifier. The interference from the hydrophillic modifier on the adsorption of magnetizing reagent on minerals is reduced. Thus, the dosage of magnetizing reagent can be lower.

Magnetic field strength for the separation at 90% passing 500 mesh using the magnetizing method is effective as low as at 2 kilogauss, as shown in Table 21. Optimum field strength is at about 10 kilogauss. Further increase of the field strength does not improve the separation. This phenomena is the same as that for the Illinois No. 6. This indicates that minerals of the two coals ground to the same size are magnetic enhanced to about the same extent. The lowest ash content obtained in these tests is 1.32%, which represents 86% ash reduction. Coal yield is 75% (79% coal recovery).

Table 22 demonstrates the effect of reagent dosage on the processing of 90% passing 325 mesh Lower Kittanning coal. About 5 lb/ton of magnetizing reagent is sufficient. Ash content can be reduced to 1.92%, which is about 77% ash reduction. The yield of coal is 80%, which is equivalent to 84% coal recovery. Separation results at various magnetic field strengths are shown in Table 23. Again, increasing the magnetic field strength beyond 10 kilogauss provides little separation improvements.

Reagent dosage for the processing of 90% passing 200 mesh coal is also optimized at about 5 lb/ton magnetizing reagent, as shown in Table 24. Ash content can be reduced to 1.57%, which is about 83% ash reduction. The yield of coal is 76%, which is equivalent to about 80% coal recovery. Magnetic field strength for the separation is optimized at about 10 kilogauss, as shown in Table 25.

The processing of 90% passing 100 mesh coal may require less than 2.5 lb/ton magnetizing reagent. As shown in Table 26, the difference of separation performance between the use of 2.5 lb/ton and 5 lb/ton magnetizing reagent dosage is very little. Ash content can be reduced to 2.29% with 78% coal yield (81% coal recovery). This represents 70% ash reduction. Magnetic field strength study shows that 15 kilogauss is required to reach the maximum ash reduction. This higher yield strength requirement is similar to the observations on the processing of Illinois No. 6 coal for coarser particles.

Figure 2 illustrates the effects of particle sizes on the ash content and coal recovery achievable with the magnetizing reagent approach. The ability to clean the coal with this approach is proportional to the fine grinding of coal, which is consistent with the processing of Illinois No. 6 coal.

Figure 1.

Figure 2.

Table 1. Dry magnetic separation of magnetic conditioned and pulverized Illinois No. 6 table concentrate

Field Strength	Descripti	Wt. %	Ash %	Ash % Reduced
	Head	100.00	6.56	
2 Kilogauss	Non-Mag.	86.20	5.24	18.00
5 Kilogauss	Non-Mag.	87.53	6.14	18.07
8 Kilogauss	Non-Mag.	82.13	6.46	19.12
10 Kilogauss	Non-Mag.	89.60	6.29	14.09
15 Kilogauss	Non-Mag.	83.00	6.16	22.06
20 Kilogauss	Non-Mag.	93.00	6.55	7.14

Table 2. Dry magnetic separation of magnetic conditioned and pulverized Lower Kittanning table concentrate

Field Strength	Descripti	Wt. %	Ash %	Ash % Reduced
	Head	100.00	2.55	
2 Kilogauss	Non-Mag.	89.73	2.98	-4.86
5 Kilogauss	Non-Mag.	85.73	2.58	13.26
8 Kilogauss	Non-Mag.	86.00	2.55	14.00
10 Kilogauss	Non-Mag.	82.80	2.41	21.75
15 Kilogauss	Non-Mag.	89.53	2.56	10.12
20 Kilogauss	Non-Mag.	87.53	2.56	12.13

Table 3. Dry magnetic separation of magnetic conditioned and pulverized Pocahontas table concentrate

Field Strength	Descripti	Wt. %	Ash %	Ash % Reduced
	Head	100.00	3.53	
2 Kilogauss	Non-Mag.	82.33	3.77	12.07
5 Kilogauss	Non-Mag.	82.40	3.71	13.40
8 Kilogauss	Non-Mag.	83.13	3.63	14.52
10 Kilogauss	Non-Mag.	84.47	3.70	11.46
15 Kilogauss	Non-Mag.	91.67	3.50	9.11
20 Kilogauss	Non-Mag.	88.67	3.58	10.07

Table 4. Dry magnetic separation of magnetic conditioned and pulverized Illinois No. 6 heavy medium concentrate

Field Strength	Descripti	Wt. %	Ash %	Ash % Reduced
	Head	100.00	4.89	
2 Kilogauss	Non-Mag.	92.93	4.81	8.59
5 Kilogauss	Non-Mag.	96.53	4.78	5.64
8 Kilogauss	Non-Mag.	96.80	4.96	1.81
10 Kilogauss	Non-Mag.	96.67	4.91	2.93
15 Kilogauss	Non-Mag.	92.80	4.77	9.48
20 Kilogauss	Non-Mag.	96.53	4.74	6.43

Table 5. Dry magnetic separation of magnetic conditioned and pulverized Lower Kittanning heavy medium concentrate

Field Strength	Descripti	Wt. %	Ash %	Ash % Reduced
	Head	100.00	2.57	
2 Kilogauss	Non-Mag.	90.80	2.54	10.26
5 Kilogauss	Non-Mag.	89.60	2.39	16.68
8 Kilogauss	Non-Mag.	94.07	2.74	-0.29
10 Kilogauss	Non-Mag.	90.53	2.58	9.12
15 Kilogauss	Non-Mag.	92.07	2.60	6.86
20 Kilogauss	Non-Mag.	91.53	2.30	18.09

Table 6. Dry magnetic separation of magnetic conditioned and pulverized Pocahontas heavy medium concentrate

Field Strength	Descripti	Wt. %	Ash %	Ash % Reduced
	Head	100.00	3.43	
2 Kilogauss	Non-Mag.	93.47	3.50	4.62
5 Kilogauss	Non-Mag.	86.67	3.45	12.82
8 Kilogauss	Non-Mag.	90.53	3.37	11.05
10 Kilogauss	Non-Mag.	82.53	3.38	18.67
15 Kilogauss	Non-Mag.	88.20	3.47	10.77
20 Kilogauss	Non-Mag.	81.07	3.21	24.13

Table 7. Dry magnetic separation of magnetic conditioned and pulverized Illinois No. 6 flotation concentrate

Field Strength	Descripti	Wt. %	Ash %	Ash % Reduced
	Head	100.00	10.50	
2 Kilogauss	Non-Mag.	98.00	8.83	17.59
5 Kilogauss	Non-Mag.	99.33	8.59	18.74
8 Kilogauss	Non-Mag.	93.40	8.65	23.06
10 Kilogauss	Non-Mag.	95.27	8.62	21.79
15 Kilogauss	Non-Mag.	93.67	8.86	20.96
20 Kilogauss	Non-Mag.	96.00	8.97	17.99

Table 8. Dry magnetic separation of magnetic conditioned and pulverized Lower Kittanning flotation concentrate

Field Strength	Descripti	Wt. %	Ash %	Ash % Reduced
	Head	100.00	10.19	
2 Kilogauss	Non-Mag.	89.13	8.73	23.64
5 Kilogauss	Non-Mag.	88.53	8.49	26.24
8 Kilogauss	Non-Mag.	92.47	8.70	21.05
10 Kilogauss	Non-Mag.	87.60	8.07	30.62
15 Kilogauss	Non-Mag.	89.67	8.30	26.96
20 Kilogauss	Non-Mag.	91.73	8.10	27.08

Table 9. Dry magnetic separation of magnetic conditioned and pulverized Pocahontas flotation concentrate

Field Strength	Descripti	Wt. %	Ash %	Ash % Reduced
	Head	100.00	5.57	
2 Kilogauss	Non-Mag.	100.00	6.37	-14.36
5 Kilogauss	Non-Mag.	99.40	5.85	-4.40
8 Kilogauss	Non-Mag.	90.13	4.94	20.06
10 Kilogauss	Non-Mag.	92.67	5.00	16.81
15 Kilogauss	Non-Mag.	88.60	4.93	21.58
20 Kilogauss	Non-Mag.	89.13	4.32	30.87

Table 10. Magnetic separation of Illinois No.6 heavy medium middlings

	Wt. %	Cum.%	Ash%	Cum.Ash%	Cum.Ash Reject%	Cum. Coal Recovery %
Non-mag. Conc.	35.05	35.05	11.08	11.08	82.70	40.19
Mag-Mid.						
Mid.C	10.40	45.45	16.65	12.35	74.99	51.37
Mid-M1	4.08	49.53	23.15	13.24	70.78	55.41
Mid-M2	9.49	59.02	26.10	15.31	59.75	64.45
Mid-T	34.01	93.03	29.31	20.43	15.35	95.45
Sub-total	57.98		(26.08)			
Mag-rejec	6.97	100.00	49.43	22.45		
Total	100.00		(22.45)			

Table 11. Magnetic separation of Low. Kittanning heavy medium middlings

	Wt. %	Cum.%	Ash%	Cum.Ash%	Cum.Ash Reject%	Cum. Coal Recovery %
Non-mag. Conc.	51.91	51.91	3.94	3.94	86.61	58.85
Mag-Mid.						
Mid.C	15.62	67.53	14.21	6.32	72.07	74.67
Mid-M1	4.25	71.78	29.09	7.66	63.97	78.23
Mid-M2	6.51	78.29	31.52	9.65	50.53	83.49
Mid-T	18.99	97.28	33.24	14.25	9.20	98.45
Sub-total	45.37		(26.05)			
Mag-rejec	2.72	100.00	51.74	15.27		
Total	100.00		(15.27)			

Table 12. Magnetic separation of Pocahontas heavy medium middlings

	Wt. %	Cum.%	Ash%	Cum.Ash%	Cum.Ash Reject%	Cum. Coal Recovery %
Non-mag. Conc.	67.11	67.11	12.37	12.37	64.33	76.64
Mag-Mid.						
Mid.C	4.24	71.35	33.92	13.65	58.14	80.29
Mid-M1	2.66	74.01	42.79	14.70	53.25	82.28
Mid-M2	5.42	79.44	43.55	16.67	43.10	86.27
Mid-T	17.32	96.76	46.93	22.09	8.16	98.25
Sub-total	29.65		(44.08)			
Mag-rejec	3.23	99.99	58.87	23.27		
Total	100.00		(23.27)			

Table 13. Magnetic field strength effect on the separation of
Illinois No.6 R.O.M. coal at 90% passing 500 mesh

	Wt. %	Cum.%	Ash%	Cum.Ash%	Cum.Ash Reject%	Cum. Coal Recovery %	Modifier (lb/t)	Reagent (lb/t)
1-C	84.02	84.02	15.80	15.80	40.74	91.17	40.00	20.00
T3	2.87	86.89	54.81	17.09	33.71	92.84	2 K gauss	
T2	4.59	91.48	59.33	19.21	21.56	95.24		
T1	8.52	100.00	56.64	22.40		100.00		
	100.00		22.40					
2-C	58.75	58.75	4.73	4.73	87.55	72.05	40.00	20.00
T3	4.85	63.60	37.15	7.20	79.48	75.98	5 K gauss	
T2	7.96	71.56	45.81	11.50	63.14	81.53		
T1	28.44	100.00	49.56	22.32		100.00		
	100.00		22.32					
3-C	53.59	53.59	3.21	3.21	92.17	66.48	40.00	20.00
T3	4.85	58.44	27.44	5.22	86.12	70.99	10 K gauss	
T2	9.50	67.94	40.43	10.14	68.64	78.25		
T1	32.06	100.00	47.05	21.98		100.00		
	100.00		21.98					
4-C	58.30	58.30	3.84	3.84	89.46	71.18	40.00	20.00
T3	5.38	63.68	33.52	6.35	80.97	75.72	15 K gauss	
T2	9.26	72.94	44.86	11.24	61.41	82.20		
T1	27.06	100.00	48.20	21.24		100.00		
	100.00		21.24					
5-C	56.94	56.94	3.34	3.34	91.23	70.27	40.00	20.00
T3	4.20	61.14	32.31	5.33	84.97	73.90	18 K gauss	
T2	8.09	69.23	40.56	9.45	69.83	80.03		
T1	30.77	100.00	49.19	21.68		100.00		
	100.00		21.68					
6-C	58.63	58.63	3.83	3.83	89.63	71.96	40.00	20.00
T3	3.10	61.73	28.39	5.06	85.56	74.80	20 K gauss	
T2	7.03	68.76	39.88	8.62	72.61	80.19		
T1	31.24	100.00	50.33	21.65		100.00		
	100.00		21.65					

Table 14. Reagent dosage effect on the separation of
Illinois No.6 R.O.M. coal at 90% passing 500 mesh

	Wt. %	Cum.%	Ash%	Cum.Ash%	Cum.Ash Reject%	Cum. Coal Recovery %	Modifier (lb/t)	Reagent (lb/t)
1-C	85.68	85.68	18.34	18.34	25.35	88.62	2.00	1.00
T3	3.03	88.71	32.75	18.83	20.64	91.20	18 K gauss	
T2	4.13	92.84	35.38	19.57	13.69	94.58		
T1	7.16	100.00	40.31	21.05				
	100.00		21.05					
2-C	74.54	74.54	17.11	17.11	39.47	78.28	5.00	2.50
T3	5.91	80.45	30.78	18.11	30.84	83.46	18 K gauss	
T2	7.79	88.24	32.65	19.40	18.76	90.12		
T1	11.76	100.00	33.66	21.07				
	100.00		21.07					
3-C	60.31	60.31	15.81	15.81	54.83	64.36	10.00	5.00
T3	8.46	68.77	27.34	17.23	43.88	72.15	18 K gauss	
T2	11.75	80.52	29.22	18.98	27.61	82.70		
T1	19.48	100.00	29.92	21.11				
	100.00		21.11					
4-C	41.31	41.31	12.06	12.06	76.57	46.14	20.00	10.00
T3	9.65	50.96	26.06	14.71	64.74	55.20	18 K gauss	
T2	17.96	68.92	27.27	17.98	41.70	71.79		
T1	31.08	100.00	28.53	21.26				
	100.00		21.26					
5-C	56.94	56.94	3.34	3.34	91.23	70.27	40.00	20.00
T3	4.20	61.14	32.31	5.33	84.97	73.90	18 K gauss	
T2	8.09	69.23	40.56	9.45	69.83	80.04		
T1	30.77	100.00	49.19	21.68				
	100.00		21.68					
6-C	51.47	51.47	3.52	3.52	91.65	63.43	60.00	30.00
T3	5.40	56.87	28.46	5.89	84.58	68.36	18 K gauss	
T2	10.53	67.40	38.47	10.98	65.92	76.64		
T1	32.60	100.00	43.91	21.71				
	100.00		21.71					
7-C	70.45	70.45	6.70	6.70	75.47	81.39	80.00	40.00
T3	4.64	75.09	44.66	9.05	64.70	84.57	18 K gauss	
T2	5.86	80.95	44.28	11.60	51.21	88.61		
T1	19.05	100.00	51.73	19.24				
	100.00		19.24					

Table 15. Reagent dosage effect on the separation of
Illinois No.6 R.O.M. coal at 90% passing 325 mesh

	Wt. %	Cum.%	Ash%	Cum.Ash%	Cum.Ash Reject%	Cum. Coal Recovery %	Modifier (lb/t)	Reagent (lb/t)
1-C	81.18	81.18	17.46	17.46	33.49	85.15	2.00	1.00
T3	4.35	85.53	31.54	18.18	27.05	88.94	18 K gauss	
T2	5.93	91.46	39.08	19.53	16.17	93.52		
T1	8.54	100.00	40.30	21.31		100.00		
	100.00		21.31					
2-C	74.01	74.01	16.53	16.53	42.24	78.38	5.00	2.50
T3	5.94	79.95	31.01	17.61	33.54	83.58	18 K gauss	
T2	7.77	87.72	34.42	19.10	20.91	90.04		
T1	12.28	100.00	36.05	21.18		100.00		
	100.00		21.18					
3-C	58.65	58.65	12.69	12.69	64.15	64.62	10.00	5.00
T3	8.34	66.99	28.90	14.71	52.54	72.11	18 K gauss	
T2	12.90	79.89	32.25	17.54	32.50	83.14		
T1	20.11	100.00	33.56	20.76		100.00		
	100.00		20.76					
4-C	56.39	56.39	5.57	5.57	85.32	67.74	20.00	10.00
T3	5.54	61.93	28.91	7.66	77.83	72.75	18 K gauss	
T2	10.19	72.12	39.81	12.20	58.86	80.55		
T1	27.88	100.00	45.15	21.39		100.00		
	100.00		21.39					
5-C	51.68	51.68	3.63	3.63	91.18	63.27	40.00	20.00
T3	5.25	56.93	24.89	5.59	85.04	68.28	18 K gauss	
T2	9.82	66.75	35.39	9.97	68.71	76.35		
T1	33.25	100.00	43.99	21.28		100.00		
	100.00		21.28					
6-C	63.38	63.38	6.12	6.12	81.46	75.24	60.00	30.00
T3	4.48	67.86	40.15	8.37	72.86	78.63	18 K gauss	
T2	8.90	76.76	43.22	12.41	54.47	85.02		
T1	23.24	100.00	49.02	20.92		100.00		
	100.00		20.92					
7-C	71.59	71.59	7.50	7.50	72.25	82.11	80.00	40.00
T3	2.99	74.58	37.60	8.71	66.44	84.42	18 K gauss	
T2	7.04	81.62	45.89	11.91	49.75	89.15		
T1	18.38	100.00	52.39	19.35		100.00		
	100.00		19.35					

Table 16. Magnetic field strength effect on the separation of
Illinois No.6 R.O.M. coal at 90% passing 325 mesh

	Wt. %	Cum.%	Ash%	Cum.Ash%	Cum.Ash Reject%	Cum. Coal Recovery %	Modifier (lb/t)	Reagen (lb/t)
1-C	81.20	81.20	14.10	14.10	48.12	89.50	40.00	20.00
T3	3.36	84.56	52.98	15.64	40.06	91.53	2 K gauss	
T2	5.11	89.67	57.47	18.03	26.75	94.32		
T1	10.33	100.00	57.18	22.07				
	100.00		22.07					
2-C	58.20	58.20	6.16	6.16	83.36	69.61	40.00	20.00
T3	5.61	63.81	36.01	8.78	73.98	74.18	5 K gauss	
T2	9.52	73.33	40.26	12.87	56.18	81.43		
T1	26.67	100.00	45.38	21.54				
	100.00		21.54					
3-C	52.82	52.82	4.31	4.31	89.67	64.82	40.00	20.00
T3	4.43	57.25	29.10	6.23	83.81	68.85	10 K gauss	
T2	9.17	66.42	38.09	10.63	67.96	76.13		
T1	33.58	100.00	44.57	22.03				
	100.00		22.03					
4-C	59.55	59.55	5.28	5.28	85.10	71.49	40.00	20.00
T3	5.05	64.60	32.09	7.38	77.42	75.84	15 K gauss	
T2	8.01	72.61	41.74	11.17	61.57	81.75		
T1	27.39	100.00	47.44	21.10				
	100.00		21.10					
5-C	61.20	61.20	5.39	5.39	84.37	73.39	40.00	20.00
T3	4.71	65.91	36.02	7.58	76.33	77.21	18 K gauss	
T2	8.93	74.84	42.51	11.75	58.33	83.71		
T1	25.16	100.00	48.91	21.10				
	100.00		21.10					
6-C	60.28	60.28	5.53	5.53	84.41	72.43	40.00	20.00
T3	4.59	64.87	33.06	7.48	77.31	76.34	20 K gauss	
T2	8.20	73.07	40.47	11.18	61.79	82.55		
T1	26.93	100.00	49.07	21.38				
	100.00		21.38					

Table 17. Reagent dosage effect on the separation of
Illinois No.6 R.O.M. coal at 90% passing 200 mesh

	Wt. %	Cum.%	Ash%	Cum.Ash%	Cum.Ash Reject%	Cum. Coal Recovery %	Modifier (lb/t)	Reagent (lb/t)
1-C	85.92	85.92	17.80	17.80	26.61	89.22	1.00	0.50
T3	3.55	89.47	36.69	18.55	20.36	92.06	18 K gauss	
T2	4.78	94.25	38.30	19.55	11.58	95.78		
T1	5.75	100.00	41.93	20.84		100.00		
	100.00		20.84					
2-C	80.00	80.00	16.22	16.22	37.25	84.50	2.00	1.00
T3	4.22	84.22	33.93	17.11	30.33	88.01	18 K gauss	
T2	6.12	90.34	37.72	18.50	19.17	92.82		
T1	9.66	100.00	41.00	20.68		100.00		
	100.00		20.68					
3-C	71.00	71.00	14.40	14.40	50.27	76.51	5.00	2.50
T3	5.90	76.90	29.89	15.59	41.69	81.71	18 K gauss	
T2	9.56	86.46	35.98	17.84	24.96	89.42		
T1	13.54	100.00	37.89	20.56		100.00		
	100.00		20.56					
4-C	57.41	57.41	11.65	11.65	68.15	64.20	10.00	5.00
T3	7.98	65.39	29.23	13.80	57.04	71.35	18 K gauss	
T2	11.81	77.20	32.29	16.62	38.88	81.48		
T1	22.80	100.00	35.83	21.00		100.00		
	100.00		21.00					
5-C	58.97	58.97	4.96	4.96	86.21	71.13	20.00	10.00
T3	4.88	63.85	22.79	6.32	80.97	75.91	18 K gauss	
T2	8.84	72.69	36.57	10.00	65.72	83.03		
T1	27.31	100.00	51.03	21.21		100.00		
	100.00		21.21					
6-C	58.61	58.61	4.24	4.24	86.87	69.22	40.00	20.00
T3	5.46	64.07	24.09	5.93	79.91	74.33	18 K gauss	
T2	10.99	75.06	34.73	10.15	59.74	83.18		
T1	24.94	100.00	45.31	18.92		100.00		
	100.00		18.92					
7-C	71.89	71.89	9.21	9.21	67.17	81.76	60.00	30.00
T3	4.13	76.02	41.00	10.94	58.78	84.81	18 K gauss	
T2	7.19	83.21	44.83	13.87	42.80	89.78		
T1	16.79	100.00	51.42	20.17		100.00		
	100.00		20.17					

Table 18. Magnetic field strength effect on the separation of
Illinois No.6 R.O.M. coal at 90% passing 200 mesh

	Wt. %	Cum.%	Ash%	Cum.Ash%	Cum.Ash Reject%	Cum. Coal Recovery %	Modifier (lb/t)	Reagent (lb/t)
1-C	84.54	84.54	17.14	17.14	32.38	89.16	20.00	10.00
T3	3.72	88.26	39.73	18.09	25.49	92.01	2 K gauss	
T2	4.31	92.57	41.48	19.18	17.14	95.22		
T1	7.43	100.00	49.39	21.43				
	100.00		21.43					
2-C	71.02	71.02	10.18	10.18	65.90	80.95	20.00	10.00
T3	4.77	75.79	35.66	11.78	57.87	84.85	5 K gauss	
T2	7.72	83.51	45.27	14.88	41.39	90.21		
T1	16.49	100.00	53.19	21.20				
	100.00		21.20					
3-C	68.43	68.43	8.32	8.32	72.15	78.85	20.00	10.00
T3	5.56	73.99	29.24	9.89	64.19	83.80	10 K gauss	
T2	8.18	82.17	43.10	13.20	46.94	89.65		
T1	17.83	100.00	53.79	20.44				
	100.00		20.44					
4-C	66.14	66.14	7.22	7.22	77.61	78.00	20.00	10.00
T3	6.18	72.32	38.68	9.91	66.41	82.82	15 K gauss	
T2	7.86	80.18	43.47	13.20	50.39	88.47		
T1	19.82	100.00	54.22	21.33				
	100.00		21.33					
5-C	64.42	64.42	7.24	7.24	78.06	75.89	20.00	10.00
T3	5.48	69.90	35.22	9.43	68.98	80.40	18 K gauss	
T2	8.17	78.07	39.88	12.62	53.66	86.64		
T1	21.93	100.00	52.00	21.26				
	100.00		21.26					
6-C	66.85	66.85	7.79	7.79	75.62	78.39	20.00	10.00
T3	4.65	71.50	29.83	9.22	69.13	82.53	20 K gauss	
T2	8.29	79.79	46.17	13.06	51.21	88.21		
T1	20.21	100.00	54.14	21.36				
	100.00		21.36					

Table 19. Reagent dosage effect on the separation of
Illinois No.6 R.O.M. coal at 90% passing 100 mesh

	Wt. %	Cum.%	Ash%	Cum.Ash%	Cum.Ash Reject%	Cum. Coal Recovery %	Modifier (lb/t)	Reagent (lb/t)
1-C	67.37	67.37	14.17	14.17	53.59	72.80	2.00	1.00
T3	7.75	75.12	26.14	15.40	43.74	80.00	18 K gauss	
T2	9.92	85.04	34.40	17.62	27.15	88.20		
T1	14.96	100.00	37.36	20.57				
	100.00		20.57					
2-C	57.00	57.00	11.36	11.36	68.18	63.43	5.00	2.50
T3	8.19	65.19	22.10	12.71	59.29	71.44	18 K gauss	
T2	12.41	77.60	29.11	15.33	41.53	82.49		
T1	22.40	100.00	37.75	20.35				
	100.00		20.35					
3-C	47.59	47.59	8.29	8.29	81.03	55.11	10.00	5.00
T3	12.74	60.33	18.09	10.36	69.95	68.28	18 K gauss	
T2	12.28	72.61	27.91	13.33	53.47	79.46		
T1	27.39	100.00	40.60	20.80				
	100.00		20.80					
4-C	48.31	48.31	5.40	5.40	87.44	57.68	20.00	10.00
T3	7.99	56.30	15.38	6.82	81.52	66.22	18 K gauss	
T2	11.69	67.99	25.12	9.96	67.39	77.26		
T1	32.01	100.00	43.73	20.77				
	100.00		20.77					
5-C	38.53	38.53	4.17	4.17	92.29	46.64	40.00	20.00
T3	7.74	46.27	14.41	5.88	86.93	55.01	18 K gauss	
T2	11.52	57.79	18.38	8.37	76.77	66.88		
T1	42.21	100.00	37.88	20.83				
	100.00		20.83					
6-C	59.74	59.74	9.70	9.70	71.73	67.86	60.00	30.00
T3	6.92	66.66	27.72	11.57	62.38	74.15	18 K gauss	
T2	12.21	78.87	34.13	15.06	42.05	84.26		
T1	21.13	100.00	40.80	20.50				
	100.00		20.50					

Table 20. Reagent dosage effect on the separation of
Lower Kittanning R.O.M. coal at 90% passing 500 mesh
(wool matrix 18 K gauss)

	Wt. %	Cum.%	Ash%	Cum.Ash%	Cum.Ash Reject%	Cum. Coal Recovery %	Modifier (lb/t)	Reagent (lb/t)
1-C	88.35	88.35	5.42	5.42	26.33	89.37	5.00	2.50
T3	2.91	91.26	13.46	5.68	20.30	92.06		
T2	3.41	94.67	15.18	6.02	12.34	95.16		
T1	5.33	100.00	15.11	6.50				
	100.00		6.50					
2-C	83.73	83.73	5.03	5.03	36.19	85.14	10.00	5.00
T3	3.40	87.13	13.65	5.37	29.16	88.28		
T2	5.41	92.54	13.87	5.86	17.79	93.27		
T1	7.46	100.00	15.75	6.60				
	100.00		6.60					
3-C	80.26	80.26	1.56	1.56	81.34	84.69	20.00	10.00
T3	3.19	83.45	16.06	2.11	73.71	87.56		
T2	4.09	87.54	25.42	3.20	58.21	90.83		
T1	12.46	100.00	31.31	6.71				
	100.00		6.71					
4-C	93.03	93.03	3.72	3.72	47.33	95.87	40.00	20.00
T3	1.14	94.17	38.90	4.15	40.58	96.61		
T2	2.08	96.25	38.90	4.90	28.26	97.97		
T1	3.75	100.00	49.54	6.57				
	100.00		6.57					

Table 21. Magnetic field strength effect on the separation of
Lower Kittanning R.O.M. coal at 90% passing 500 mesh

	Wt. %	Cum.%	Ash%	Cum.Ash%	Cum.Ash Reject%	Cum. Coal Recovery %	Modifier (lb/t)	Reagent (lb/t)
1-C	85.42	85.42	3.36	3.36	57.03	88.46	20.00	10.00
T3	3.25	88.67	21.56	4.03	46.54	91.19	2 K Gauss	
T2	4.53	93.20	25.15	5.05	29.49	94.82		
T1	6.80	100.00	28.91	6.68				
	100.00		6.68					
2-C	80.12	80.12	2.15	2.15	74.10	83.98	20.00	10.00
T3	3.87	83.99	17.14	2.84	64.12	87.42	5 K Gauss	
T2	4.31	88.30	23.42	3.85	48.94	90.95		
T1	11.70	100.00	27.85	6.65				
	100.00		6.65					
3-C	76.05	76.05	1.48	1.48	83.40	80.37	20.00	10.00
T3	3.12	79.17	15.20	2.02	76.40	83.21	10 K Gauss	
T2	5.99	85.16	21.51	3.39	57.40	88.26		
T1	14.84	100.00	26.25	6.78				
	100.00		6.78					
4-C	74.96	74.96	1.39	1.39	84.92	79.40	20.00	10.00
T3	3.23	78.19	12.14	1.83	79.25	82.45	15 K Gauss	
T2	6.56	84.75	18.11	3.09	62.05	88.22		
T1	15.25	100.00	28.13	6.91				
	100.00		6.91					
5-C	74.34	74.34	1.32	1.32	85.74	78.78	20.00	10.00
T3	4.18	78.52	14.43	2.02	76.97	82.62	18 K Gauss	
T2	6.05	84.57	19.76	3.29	59.59	87.83		
T1	15.43	100.00	26.57	6.88				
	100.00		6.88					
6-C	73.71	73.71	1.37	1.37	85.49	78.14	20.00	10.00
T3	4.03	77.74	12.26	1.93	78.39	81.94	20 K Gauss	
T2	5.55	83.29	18.83	3.06	63.38	86.78		
T1	16.71	100.00	26.38	6.96				
	100.00		6.96					

Table 22. Reagent dosage effect on the separation of
Lower Kittanning R.O.M. coal at 90% passing 325 mesh
(wool matrix 18 K gauss)

	Wt. %	Cum.%	Ash%	Cum.Ash%	Cum.Ash Reject%	Cum. Coal Recovery %	Modifier (lb/t)	Reagent (lb/t)
1-C	84.41	84.41	5.02	5.02	35.80	85.84	5.00	2.50
T3	4.16	88.57	13.69	5.43	27.17	89.68		
T2	5.51	94.08	13.82	5.92	15.63	94.77		
T1	5.92	100.00	17.45	6.60				
	100.00		6.60					
2-C	80.05	80.05	1.92	1.92	77.23	84.20	10.00	5.00
T3	3.67	83.72	17.03	2.58	67.97	87.46		
T2	4.92	88.64	21.08	3.61	52.61	91.63		
T1	11.36	100.00	31.22	6.75				
	100.00		6.75					
3-C	89.96	89.96	3.61	3.61	50.04	92.74	20.00	10.00
T3	2.59	92.55	20.24	4.08	41.97	94.95		
T2	2.68	95.23	31.25	4.84	29.09	96.92		
T1	4.77	100.00	39.55	6.50				
	100.00		6.50					
4-C	90.59	90.59	3.33	3.33	54.29	93.76	40.00	20.00
T3	2.03	92.62	28.76	3.89	45.45	95.31		
T2	2.48	95.10	35.26	4.71	32.20	97.03		
T1	4.90	100.00	43.34	6.60				
	100.00		6.60					

Table 23. Magnetic field strength effect on the separation of
Lower Kittanning R.O.M. coal at 90% passing 325 mesh

	Wt. %	Cum.%	Ash%	Cum.Ash%	Cum.Ash Reject%	Cum. Coal Recovery %	Modifier (lb/t)	Reagen (lb/t)
1-C	88.67	88.67	4.15	4.15	41.87	90.73	10.00	5.00
T3	2.86	91.53	14.20	4.46	35.45	93.35	2 K Gauss	
T2	3.93	95.46	21.12	5.15	22.34	96.66		
T1	4.54	100.00	31.20	6.33				
	100.00		6.33					
2-C	84.29	84.29	2.90	2.90	62.28	87.52	10.00	5.00
T3	4.21	88.50	17.49	3.59	50.91	91.23	5 K Gauss	
T2	4.56	93.06	27.27	4.75	31.72	94.78		
T1	6.94	100.00	29.58	6.48				
	100.00		6.48					
3-C	83.38	83.38	2.61	2.61	66.05	86.77	10.00	5.00
T3	3.75	87.13	16.23	3.20	56.55	90.12	10 K Gauss	
T2	4.56	91.69	23.08	4.19	40.14	93.87		
T1	8.31	100.00	30.90	6.41				
	100.00		6.41					
4-C	80.69	80.69	2.41	2.41	70.85	84.37	10.00	5.00
T3	3.96	84.65	13.86	2.95	62.62	88.03	15 K Gauss	
T2	5.32	89.97	21.25	4.03	45.67	92.52		
T1	10.03	100.00	30.40	6.67				
	100.00		6.67					
5-C	80.41	80.41	2.38	2.38	71.05	84.05	10.00	5.00
T3	3.90	84.31	15.40	2.98	61.96	87.59	18 K Gauss	
T2	5.42	89.73	20.66	4.05	45.02	92.19		
T1	10.27	100.00	29.02	6.61				
	100.00		6.61					
6-C	80.24	80.24	2.63	2.63	67.93	83.63	10.00	5.00
T3	4.26	84.50	16.55	3.33	57.21	87.44	20 K Gauss	
T2	5.82	90.32	21.97	4.53	37.78	92.30		
T1	9.68	100.00	25.65	6.58				
	100.00		6.58					

Table 24. Reagent dosage effect on the separation of
Lower Kittanning R.O.M. coal at 90% passing 200 mesh
(wool matrix 18 K gauss)

	Wt. %	Cum.%	Ash%	Cum.Ash%	Cum.Ash Reject%	Cum. Coal Recovery %	Modifier (lb/t)	Reagent (lb/t)
1-C	76.19	76.19	1.57	1.57	82.59	80.53	10.00	5.00
T3	4.37	80.56	13.10	2.20	74.26	84.60		
T2	5.27	85.83	19.70	3.27	59.14	89.15		
T1	14.17	100.00	28.68	6.87				
	100.00		6.87					
2-C	86.92	86.92	2.58	2.58	63.06	90.15	20.00	10.00
T3	3.23	90.15	19.06	3.17	52.91	92.93		
T2	3.88	94.03	25.54	4.09	36.59	96.01		
T1	5.97	100.00	37.27	6.07				
	100.00		6.07					
3-C	86.77	86.77	2.58	2.58	63.54	90.06	40.00	20.00
T3	2.49	89.26	19.75	3.06	55.53	92.19		
T2	3.73	92.99	24.57	3.92	40.60	95.19		
T1	7.01	100.00	35.57	6.14				
	100.00		6.14					
4-C	85.94	85.94	2.93	2.93	59.25	88.92	60.00	30.00
T3	2.89	88.83	20.68	3.51	49.58	91.36		
T2	4.34	93.17	22.44	4.39	33.83	94.95		
T1	6.83	100.00	30.55	6.18				
	100.00		6.18					

Table 25. Magnetic field strength effect on the separation of
Lower Kittanning R.O.M. coal at 90% passing 200 mesh

	Wt. %	Cum.%	Ash%	Cum.Ash%	Cum.Ash Reject%	Cum. Coal Recovery %	Modifier (lb/t)	Reagen- (lb/t)
1-C	88.46	88.46	3.47	3.47	47.97	90.74	10.00	5.00
T3	2.39	90.85	14.09	3.75	42.27	92.93	2 K Gauss	
T2	3.58	94.43	22.24	4.45	28.77	95.88		
T1	5.57	100.00	30.47	5.90				
	100.00		5.90					
2-C	85.36	85.36	2.65	2.65	62.36	88.41	10.00	5.00
T3	3.10	88.46	12.73	3.00	55.80	91.29	5 K Gauss	
T2	3.89	92.35	23.34	3.86	40.69	94.46		
T1	7.65	100.00	32.01	6.01				
	100.00		6.01					
3-C	83.07	83.07	2.09	2.09	71.40	86.59	10.00	5.00
T3	3.23	86.30	14.31	2.55	63.78	89.54	10 K Gauss	
T2	4.42	90.72	19.68	3.38	49.45	93.32		
T1	9.28	100.00	32.40	6.07				
	100.00		6.07					
4-C	86.12	86.12	2.28	2.28	67.44	89.56	10.00	5.00
T3	2.90	89.02	16.26	2.74	59.62	92.14	15 K Gauss	
T2	4.23	93.25	26.71	3.82	40.88	95.44		
T1	6.75	100.00	36.47	6.03				
	100.00		6.03					
5-C	85.64	85.64	2.02	2.02	70.68	89.17	10.00	5.00
T3	2.89	88.53	17.62	2.53	62.05	91.70	18 K Gauss	
T2	4.29	92.82	27.47	3.68	42.07	95.01		
T1	7.18	100.00	34.57	5.90				
	100.00		5.90					
6-C	84.02	84.02	1.83	1.83	74.96	87.88	10.00	5.00
T3	3.44	87.46	16.84	2.42	65.52	90.93	20 K Gauss	
T2	4.33	91.84	23.50	3.43	48.76	94.50		
T1	8.16	100.00	36.64	6.14				
	100.00		6.14					

Table 26. Reagent dosage effect on the separation of
Lower Kittanning R.O.M. coal at 90% passing 100 mesh
(wool matrix 18 K gauss)

	Wt. %	Cum.%	Ash%	Cum.Ash%	Cum.Ash Reject%	Cum. Coal Recovery %	Modifier (lb/t)	Reagent (lb/t)
1-C	76.81	76.81	2.40	2.40	69.63	79.81	5.00	2.50
T3	5.97	82.78	10.40	2.98	59.40	85.51		
T2	5.87	88.65	15.79	3.83	44.13	90.77		
T1	11.35	100.00	23.60	6.07				
	100.00		6.07					
2-C	78.44	78.44	2.29	2.29	69.76	81.48	10.00	5.00
T3	4.52	82.96	12.01	2.82	60.62	85.71		
T2	6.71	89.67	17.39	3.91	40.98	91.61		
T1	10.33	100.00	23.60	5.94				
	100.00		5.94					
3-C	80.69	80.69	2.61	2.61	62.66	83.28	20.00	10.00
T3	4.65	85.34	11.95	3.12	52.81	87.62		
T2	5.50	90.84	17.28	3.98	35.96	92.44		
T1	9.16	100.00	22.17	5.64				
	100.00		5.64					
4-C	79.84	79.84	2.45	2.45	64.04	82.36	40.00	20.00
T3	4.58	84.42	12.26	2.98	53.72	86.61		
T2	6.33	90.75	14.11	3.76	37.30	92.36		
T1	9.25	100.00	21.94	5.44				
	100.00		5.44					

Table 27. Magnetic field strength effect on the separation of
Lower Kittanning R.O.M. coal at 90% passing 100 mesh

	Wt. %	Cum.%	Ash%	Cum.Ash%	Cum.Ash Reject%	Cum. Coal Recovery %	Modifier (lb/t)	Reagent (lb/t)
1-C	82.56	82.56	3.76	3.76	48.52	84.55	10.00	5.00
T3	4.31	86.87	11.58	4.15	40.24	88.61	2 K Gauss	
T2	5.88	92.75	16.73	4.95	23.93	93.82		
T1	7.25	100.00	19.94	6.03				
	100.00		6.03					
2-C	79.67	79.67	3.00	3.00	60.62	82.27	10.00	5.00
T3	4.72	84.39	11.76	3.49	51.48	86.71	5 K Gauss	
T2	5.52	89.91	15.71	4.24	37.19	91.66		
T1	10.09	100.00	22.41	6.07				
	100.00		6.07					
3-C	79.23	79.23	3.01	3.01	61.35	81.90	10.00	5.00
T3	4.48	83.71	10.59	3.42	53.66	86.17	10 K Gauss	
T2	5.98	89.69	14.67	4.17	39.44	91.61		
T1	10.31	100.00	23.65	6.17				
	100.00		6.17					
4-C	78.43	78.43	2.42	2.42	67.97	81.41	10.00	5.00
T3	4.77	83.20	10.09	2.91	59.18	85.85	15 K Gauss	
T2	5.45	88.63	15.10	3.66	45.31	90.77		
T1	11.37	100.00	23.61	5.93				
	100.00		5.93					
5-C	78.10	78.10	2.48	2.48	68.09	81.08	10.00	5.00
T3	4.78	82.88	10.72	2.96	59.65	85.63	18 K Gauss	
T2	6.07	88.95	14.15	3.72	45.50	91.18		
T1	11.05	100.00	24.99	6.07				
	100.00		6.07					
6-C	77.45	77.45	2.33	2.33	70.37	80.55	10.00	5.00
T3	5.25	82.70	8.85	2.74	62.74	85.65	20 K Gauss	
T2	5.65	88.35	13.08	3.40	50.60	90.88		
T1	11.65	100.00	26.42	6.09				
	100.00		6.09					

END

**DATE
FILMED**

8 / 25 / 92