MAY 21 1962

ATOMICS INTERNATIONAL
A Division of North American Aviation, Inc.

MASTER

Do not remove
this sheet

AI-MEMO ~~6416~~

This document contains 11 pages

This is copy _____ of _____ series _____

UNCLASSIFIED

Security Classification

*AI-MEMOs are working papers and may be expanded,
modified, or withdrawn at any time,
and are intended for internal use only.*

NOTICE

This document involves confidential PROPRIETARY information of North American Aviation, Inc., and all design, manufacturing, reproductions, use, and sale rights regarding the same are expressly reserved. It is submitted under a confidential relationship for a specified purpose, and the recipient, by accepting this document assumes custody and control and agrees that (a) this document will not be copied or reproduced in whole or in part, nor its contents revealed in any manner or to any person except to meet the purpose for which it was delivered, and (b) any special features peculiar to this design will not be incorporated in other projects.

When this document is not further required for the specific purposes for which it was submitted, the recipient agrees to return it.

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency Thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

DISCLAIMER

Portions of this document may be illegible in electronic image products. Images are produced from the best available original document.

ATOMICS INTERNATIONAL A Division of North American Aviation, Inc.		AI-TDR TDR NO 6416	APPROVALS <i>[Signature]</i> 6/15/61
TECHNICAL DATA RECORD		PAGE 1 OF 11	<i>[Signature]</i>
AUTHOR W. T. Smith * (5)		DEPT & GROUP NO 793-32	
		DATE May 31, 1961	
		GO NO 2374	
TITLE Experimental Apparatus and Techniques for High Temperature Compatibility Studies		S A NO TWR 23651	RECOMMENDED FOR OUTSIDE DISTRIBUTION ☐ YES ☒ NO <i>[Signature]</i> SIGNATURE
PROGRAM NASA Contract 5-453	SUBACCOUNT TITLE NASA Study Program Assistance to Rocketdyne IDWA		
DISTRIBUTION USE AN ASTERISK (*) TO INDICATE THOSE WHO ARE TO RECEIVE COMPLETE COPIES W. J. Anderson * D. E. Ellis * W. J. Hallett * B. R. Hayward * R. D. Moeller * J. P. Page * D. I. Siniger * <i>[Signature]</i> Holland-798	STATEMENT OF PROBLEM The development of apparatus and laboratory techniques for the study of materials compatibility with 1500°F to 2200°F potassium was required for this project.		
ABSTRACT Techniques for: 1) corrosion tab preparation, 2) dry box capsule filling and sampling, and 3) vacuum filling and sampling were developed and are described.			
Apparatus for: 1) rotating capsule testing to 2000°F, 2) rotating capsule testing to 2400°F, 3) anisothermal "see-saw" capsule testing are described.			
The first several copies of page 1 of this TDR are for tear-off and retention. The TDR can then be passed on to others who wish to see it. Please do NOT remove the final copy of page 1.			

EXPERIMENTAL TECHNIQUES AND TEST APPARATUS

This report was prepared specifically to describe experimental test equipment, conditions and laboratory techniques established during the course of a study of 1500°F to 2200°F potassium corrosion.

I. LABORATORY TECHNIQUES

The laboratory techniques used can be broken down into the following phases: Sample tab preparation, typical Hastelloy-X and Cb-1%Zr capsule fabrication, dry-box filling, closure and sampling techniques, vacuum potassium purification, capsule-filling and sampling methods.

Sample Tab Preparation: In as much as the tabs constitute the prime specimens for investigation in capsule testing, the data extracted from such tests are dependent upon numerous factors applicable to their preparation and test conditions. The following measurements and examinations were made on each sample tab before and after testing.

1. Thickness to 0.0001"
2. Weight to 0.0001 grams
3. Metallographic examination
4. Knoop microhardness traverse
5. Bend test using "Vee" block and appropriate mandril
6. Chemical analysis (if necessary)

A careful cleaning process was used before the initial and final weighings; this consisted of scrubbing in distilled water, following with acetone or carbon tetrachloride and allowing a complete drying period.

Typical Encapsulating Techniques: Figures 1 and 2 are schematics of two different types of test using Hastelloy-X and Cb-1%Zr as the container for tabs in liquid potassium. The Hastelloy-X container exhibits certain limitations of time and temperature due to the high

ATOMICS INTERNATIONAL

A Division of North American Aviation, Inc

NO AI-TDR-6416

DATE May 31, 1961

PAGE 3 OF 11

vapor pressure of potassium at elevated temperatures. Therefore, the majority of tests of this type were limited to temperatures of 1800°F for long term exposures (up to 1000 hours), while at the higher temperatures of 1900°F or 2000°F the exposure period must be lowered to 200 and 100 hours respectively.

The Cb-1%Zr capsule shown in Figure 2 proved very successful for 1900°F and 2000°F tests. This type capsule requires a dynamic vacuum, an outer oxidation shield (Inconel-X), and a inner reaction "buffer" (tantalum) when exposed in standard furnaces. Tests at temperatures greater than 2000°F required the design of more elaborate test equipment such as the Dynamic Vacuum Apparatus (Figure 5). Columbium-1%Zr capsules were tested at 2100°F and 2200°F without the use of oxidation and reaction shielding in the Dynamic Vacuum Apparatus, which will be described subsequently.

Potassium filling and capsule closure was accomplished in an argon-filled dry box with a zirconium hot trap "getter" back-purge attachment, and with TIG welding while in this inert atmosphere.

Two methods of sampling were (a) to withdraw a liquid potassium sample with a glass eye dropper before and after capsule tests, (b) to use a thin wall stainless tube having a piano wire stretched taut across one end; a core sample could be obtained from solid potassium by forcing the tube into the potassium and rotating the tube, thus shearing off a solid sample with soluble constituents intact.

Potassium Purification and Sampling Methods: A need for further experimentation using purified potassium was determined from the preliminary phases of capsule tests. This required a critical review of previous methods and resulted in the fabrication of a closed system purification apparatus. The apparatus used is shown schematically in Figure 3 and portrays the following conditions to obtain potassium purity.

1. A completely closed system which is evacuated during transferral of potassium to eliminate gaseous contamination.

ATOMICS INTERNATIONAL

A Division of North American Aviation Inc.

NO AI-TDR-6416
DATE May 31, 1961
PAGE 4 OF 11

2. Sampling methods before and after purification to establish standards.
3. Hot trap purification of potassium using approximately 3200 square inches of zirconium foil held at 1200°F for 50 hours.
4. Stainless steel 40 micron mesh filter to remove precipitant contamination.
5. A method of resistance welding developed by Rocketdyne to seal the Cb-1%Zr capsules while under vacuum.

Figure 3, item 3 shows the various steps in the procedures used, and this operating procedure may be broken down into three major phases:

- 1) sampling of as-received potassium, 2) hot trap purification, and
- 3) sampling of purified potassium and capsule filling.

1. The sampling apparatus used for as-received potassium is not shown in Figure 3 since it has essentially the same design and operating procedure as item 2, Figure 3 with the exception of capsule attachments.
2. Immediately after the vacuum sampling of as-received potassium has been accomplished the excess potassium is drained into the hot trap container vessel and back-purged with argon cover gas to approximately 1 psi. The control valves are then closed, thus isolating the system prior to heating the assembly to 1200°F.
3. After purification the potassium is ready to be transferred into the evacuated sample and capsule filling apparatus (item 2, Figure 3). The potassium is maintained at $< 250^{\circ}\text{F}$ due to the necessary use of swage-lock connectors (using teflon seals) to make the metal-to-pyrex junctions. A small amount of potassium is flushed through the piping and discarded into the lower sump to clean the system of possible impurities. The drain valve is then closed and fresh potassium is admitted into the upper reservoir until the homogeneous solution reached the entry ports to the sample bulbs and capsules. Since all of these ports are at the same elevation, simultaneous filling of the metered

volumes between the entry port and the capillary freeze seals takes place. When the freeze seals are established the control valves are closed and the excess potassium drained into the sump reservoir. The freeze seals are then heated and the metered volume of potassium collected in the sample bulbs and capsules and detached from the system by fusing the glass at the freeze seals. The six Cb-1%Zr capsules are hydraulically crimped midway on the 1/4" tubing neck and are resistance welded by Rocketdyne shops. Figure 6 is an x-ray photograph of the columbium capsules with potassium after removing from the purification apparatus.

II. TEST APPARATUS

A detailed description of the test equipment is given on the following items: low temperature rotating furnace and capsule design, high-temperature rotating apparatus, description of see-saw furnace test.

Low Temperature Rotating Furnace and Capsule Design: Two rotating furnace rigs (Figure 4) were fabricated in the later stages of this program to accelerate capsule testing with purified potassium. Due to cancellation of project funds however, these test rigs were never used; they are in this report as a prospect for future corrosion testing. The Cb-1%Zr capsules are filled with high purity potassium and sealed under vacuum by resistance welding.

The capsules are then wrapped with tantalum foil and inserted into a Hastelloy-X capsule which is "TIG" welded in a inert dry-box atmosphere. These capsules are exposed at various temperatures and immediately quenched and core sampled to determine solubility of columbium in potassium.

High Temperature Capsule Rotating Apparatus: The need for this apparatus was satisfied by the design and fabrication of the unit

ATOMICS INTERNATIONAL

A Division of North American Aviation, Inc

NO AI-TDR-6416

DATE May 31, 1961

PAGE 6 OF 11

described below, and seen in Figure 3. The entire vacuum system to the fore pump is pyrex glass with the exception of the hot zone, which is a mullite combustion chamber. This required a vacuum tight mullite-to-pyrex fused seal which is relatively easy to effect. At a furnace temperature of 2400°F the indicated vacuum is 1.5×10^{-6} mm of Hg with a leak rate of only 0.1 microns/hr. The Cb-1%Zr potassium-filled capsules are contained in a columbium holder in the hot zone and supported on a Hastelloy-X and stainless shaft extending through graphite bearings at each end. Capsule rotation is achieved by means of a permanent-magnet coupling (requiring no seals) between a set of magnets attached to the inner shaft and a matching outer set attached to a rotating drive mechanism.

Reversible See-Saw Furnace Test: This test was initiated primarily to determine anisothermal effects in a bi-metal system. The capsule fabrication and filling method is the same as in Figure 2 with the exception of fixed sample tabs of Cb-1%Zr at one end and Hastelloy-X at the opposite end of the capsule. The operational procedure is to hold the assembly at 2000°F for 24 hours with the Cb-1%Zr tab down, then cool to 1500°F and invert the capsule and furnace to allow the Hastelloy-X tab contact with liquid potassium.

FIGURE# 1
 (ENCAPSULATING)

FIGURE# 2
 (ENCAPSULATING)

AS-RECEIVED K

POTASSIUM PURIFICATION APPARATUS

FIGURE #3

ITEM # I

PHASE PROCEDURE

ITEM #3

CAPSULE DETAIL

FIGURE #4
 (ROTATING APPARATUS FOR CAPSULE TESTING, 2000 F)

FIGURE #3. DYNAMIC CAPSULE TEST RIG

Figure 6. Columbian Capsules - Potassium Filled (X-ray Photograph)