**Martin Marietta Energy Systems, Inc., Engineering
Process Engineering**

**INVESTIGATION OF CELOTEX™
CHARRING DEPTHS IN THE DT-18
SHIPPING CONTAINER**

J. C. Anderson

Date Published - March 1992

MARTIN MARIETTA ENERGY SYSTEMS, INC.
Oak Ridge, Tennessee 37831
managing the

Oak Ridge National Laboratory
Oak Ridge K-25 Site

Oak Ridge Y-12 Plant
Paducah Gaseous Diffusion Plant

for the
U.S. DEPARTMENT OF ENERGY
under Contract No. DE-AC05-84OR21400

MASTER

CONTENTS

	Page
LIST OF FIGURES	v
LIST OF TABLES	vii
ACKNOWLEDGMENTS	ix
ABSTRACT	xi
INTRODUCTION	1
INVESTIGATION OF CELOTEX™ INSULATING MATERIAL IN DT-18 PACKAGES FOLLOWING THERMAL TESTS	3
CELOTEX™ CHARRING TEMPERATURES	5
DT-18 HEATING 7.1 COMPUTER MODELS	7
DISCUSSION OF RESULTS	13
CONCLUSIONS	17
REFERENCES	19
APPENDICES	
Appendix 1 Post Thermal Test Measurements and Observations	21
Appendix 2 One-Dimensional DT-18 HEATING Model - Side	29
Appendix 3 One-Dimensional DT-18 HEATING Model - Top	33
Appendix 4 One-Dimensional DT-18 HEATING Model - Bottom	37

LIST OF FIGURES

	Page
1. DT-18 shipping container	2
2. One-dimensional DT-18 HEATING model geometries	8
3. Temperature of Celotex™ insulating material in the DT-18 package	14
4. Celotex™ charring depth as a function of time in the DT-18 package	15
A1.1 DT-18 Celotex™ inserts	24

LIST OF TABLES

	Page
1. Thermal properties of materials used in the analyses	9
2. Natural convection correlation constants	12

ACKNOWLEDGMENTS

The author acknowledges the help and influence of several individuals who aided in the preparation of this document. M. R. Feldman and W. R. Williams of the Engineering Analysis Department were especially instrumental in providing original ideas, support, and comments as this work progressed.

The members of the Energy Systems Independent Review Group Committee and the Packaging Group of the Y-12 Plant Systems Safety Engineering Division and the Weapons Support Group of the Mechanical Design Division were most helpful throughout this project. E. Stumpf of the Y-12 Packaging Program and S. D. Moses of the System Safety Engineering Division gave continuous input as well as support during this project.

This project was performed at the request of and was funded exclusively by the Y-12 Packaging Program.

ABSTRACT

Celotex™, the insulating material used between the outer and inner containers of the DT-18 shipping package, undergoes decomposition, combustion, or both when heated to temperatures exceeding 150°C. Several DT-18 packages that had previously undergone hypothetical thermal accident testing were opened, and Celotex™ charring depths ranging from 1/2 to 1 1/2 in. were recorded. The majority of char depth data taken was between 3/4 and 1 1/4 in. One-dimensional HEATING 7.1 models of the DT-18 package were developed. HEATING predicts charring depths of 1 to 1 1/8 in., which are in good agreement with measured values. Both experimental and analytical data indicate that charring is fairly uniform over the DT-18 package.

INTRODUCTION

Celotex™, the insulating material used in the DT-18 and other shipping packages, is a fiberboard made from sugar cane or tree fiber bonded together with an organic glue. Stacked rings and disks of Celotex™ are used to fill the space between the outer and inner containers in the DT-18 shipping package. A sketch of the DT-18 package is shown in Fig. 1.

When heated beyond certain temperatures, Celotex™ undergoes a process known as pyrolysis, which is decomposition in a reducing atmosphere (i.e., no oxygen or not enough oxygen to support total combustion). In addition to the decomposition process, some combustion will occur if oxygen is available. Once the decomposition and combustion processes have occurred, the remaining Celotex™ material can best be described as char.

The purposes of this report are to establish an approximate charring temperature or range of temperatures, present experimental charring depth data from thermally tested DT-18 packages, and to compare these measured charring depths with those calculated by HEATING 7.1, a finite difference transient heat transfer computer code.

Note : All dimensions are in cm.

Fig. 1. DT-18 shipping container.

INVESTIGATION OF CELOTEX™ INSULATING MATERIAL IN DT-18 PACKAGES FOLLOWING THERMAL TESTS

The Celotex™ insulating material from several DT-18 packages was investigated following regulatory furnace tests. The thermal tests were conducted in the B-1023 furnace at the Y-12 Plant in Oak Ridge, Tennessee. The packages were subjected to furnace temperatures ranging from approximately 800 to 835°C. In order to comply with the requirements of Title 10 CFR 71.73(c)(3),¹ each package was left in the furnace for at least 30 min. After the packages were allowed to cool sufficiently, the containers were opened and the Celotex™ insulating materials were observed. Observations made and measurements taken from each package are presented in Appendix 1.

Measurements of the overall thicknesses indicate that the insulation shrinks approximately 1/4 to 1/2 in. as a result of the heat. Approximately 3/4 to 1 in. of the Celotex™ material was charred and could be easily scraped away. The next layer of solid material, approximately 1/4 to 1/2 in., was slightly discolored (i.e., material was brown rather than the original white); however, the material maintained the density of the original unheated Celotex™. Most of the material past depths of 1 1/2 in. on the top, bottom, and sides of the package appeared to have been unaffected. Therefore, based on visual inspection, charring depths of 1/2 to 1 1/2 in. occur in the DT-18 shipping package. No charring had occurred in the insulation in contact with the inner cylinder. Some streaking and condensed tar were observed on the inner cylinders.

CELOTEX™ CHARRING TEMPERATURES

Thermal tests were conducted on blocks of Celotex™ insulation (8 in. x 4 in. with nominal thickness of 2 in.) at furnace temperatures up to 350°F (177°C). The following results were documented:²

At 300°F the insulation had a slightly darkened appearance. The insulation at 325°F was noticeably darker and the adhesive used to bond the 1/2-inch layers together began to separate. A temperature of 350°F resulted in a very dark brown color with the layers separating very easily.

Therefore, based on this information, it can be concluded that the Celotex™ charring process begins somewhere between 300 and 350°F (149 to 177°C).

DT-18 HEATING 7.1 COMPUTER MODELS

Three one-dimensional (1-D) models of the DT-18 shipping container were constructed using HEATING 7.1, a multidimensional finite difference transient heat transfer computer code.³

The justification for using 1-D models is presented in an earlier report, *Effect of Gray-Body Interchange Factor and Radiating Temperature on the Thermal Response of the DT-18 Shipping Container*.⁴ This report contains data which show that the temperatures calculated by the 1-D DT-18 models are within 0.1°C of temperatures calculated by a full, two-dimensional (2-D) model of the DT-18 package. A 1-D (r) model was constructed to calculate the charring depth through the side of the DT-18 package. One-dimensional (z) models were constructed to calculate the charring depths at the top and bottom of the DT-18 package. Sketches of the three 1-D models are shown in Fig. 2. The DT-18 side model was constructed at a height corresponding to the seal location at the inner container; therefore, plywood was not included. The top and bottom models were constructed at locations corresponding to the centerline of the container. The models consist of two materials, stainless steel, and Celotex™. Both the outer and inner containers are modeled as stainless steel. Celotex™ is a fiberboard insulation used between the outer drum and inner container. Thermal properties for both stainless steel and Celotex™ are presented in Table 1. As Celotex™ chars, its thermal properties change. However, no properties for charred Celotex™ were available. Therefore, for this analysis, properties of charred and uncharred Celotex™ were taken to be equivalent.

As a matter of clarification, the outer drum of the DT-18 package could be constructed of either stainless steel (304) or carbon steel. Both materials have been used in the past. Outer container temperatures calculated by HEATING models with stainless and carbon steel outer drums indicate that the stainless steel drum heats up more quickly than the carbon steel drum. However, after 30 min the difference in the outer container temperatures are insignificant (less than 1°C). Therefore, predicted charring depths resulting from a 30-min furnace test are identical for packages using carbon and stainless steel outer drums.

Polyurethane foam is commonly used as the packing material inside the inner container. However, since the thermal conductivity of polyurethane foam is relatively low, approximately 0.05 to 0.06 W/m-K, most of the heat absorbed by the inner container will be stored rather than transferred through to the polyurethane. Therefore, as a conservative measure, the contents of the inner container which would normally include the polyurethane insulation and the payload were not modeled, and the inner surface of the inner container was modeled as an insulated boundary.

It should be noted that the heat transfer within the package is modeled solely as conduction. In actuality, Celotex™ will decompose (and burn if oxygen is present) at high temperatures such as those achieved during furnace tests. This process, known as pyrolysis, will affect the temperature distribution within the package. However, current analyses attempting to model the pyrolysis process do so by introducing a volumetric heat generation

Fig. 2. One-dimensional DT-18 HEATING model geometries.

Table 1. Thermal properties of materials used in the analyses

Material	Temperature (K)	Thermal conductivity (W/m-K)	Density (kg/m³)	Specific heat (J/kg-K)
Stainless steel ¹	200	12.6	7900 ^a	402
	300	14.9		477
	400	16.6		515
	600	19.8		557
	800	22.6		582
	1000	25.4		611
	1200	28.0		640
Celotex TM ²	298	0.053	270 ^a	1280
	359	0.059		1506
	419	0.063		1745
	499	0.065		2046
	551	0.051		2063

^a For modeling purposes, density was considered as a constant (temperature independent).

- Sources :
1. *Safety Analysis Report for Packaging, Oak Ridge Y-12 Plant, Model DT-23 Package with Subassembly Contents (U)*, Y/LF-51-IA/R1, October 26, 1990.
 2. L. C. Sanchez, R. S. Longenbaugh, M. Moss, G. M. Haseman, W. E. Fowler, and E. P. Roth, *Thermal Analysis of the 10-Gallon and the 55-Gallon DOT-6M Containers with Thermal Boundary Conditions Corresponding to 10 CFR 71 Normal Transport and Accident Conditions*, Sandia Report SAND87-1896 TTC-0748, 1988.

rate in the inner container to simulate the condensation and convection of hot gases generated during the heating of Celotex™.⁵ Previous analyses have shown that this heat generation has a very significant effect on the temperature of the inner container and the surrounding Celotex™. However, the effect on the outer 2 in. of the DT-18 package, which is the region of interest in this study, is insignificant.

The boundary conditions applied to the DT-18 HEATING models are intended to represent exactly the hypothetical thermal accident conditions called for in Title 10 CFR 71.73(c)(3).¹ The sides, top, and bottom of the package therefore receive heat due to radiative exchange with the furnace interior and by natural convection with the air in the furnace.

The total heat added to the package can be calculated as

$$Q_{\text{total}} = Q_{\text{rad}} + Q_{\text{conv}}. \quad (1)$$

The net radiative heat flow from the furnace to the package (Q_{rad}) can be calculated as

$$Q_{\text{rad}} = A_P \mathcal{F}_{P-F} \sigma (T_F^4 - T_P^4), \quad (2)$$

where

$$\begin{aligned} \sigma &= \text{Stefan-Boltzmann constant,} \\ T_F &= \text{furnace temperature,} \\ T_P &= \text{package surface temperature,} \\ A_P &= \text{package surface area,} \\ \mathcal{F}_{P-F} &= \text{gray-body interchange factor between package and furnace interior.} \end{aligned}$$

The gray-body interchange factor between the package and the furnace interior ($\mathcal{F}_{P-F}$) can be calculated as:⁶

$$\mathcal{F}_{P-F} = [1/\epsilon_P + A_P/A_F(1/\epsilon_F - 1)]^{-1}, \quad (3)$$

where

$$\begin{aligned} \epsilon_P &= \text{package emissivity,} \\ \epsilon_F &= \text{furnace emissivity,} \\ A_P/A_F &= \text{ratio of package surface area to furnace surface area.} \end{aligned}$$

Title 10 CFR 71 states that a package absorptivity of 0.8, a furnace emissivity of 0.9, and a package-to-furnace surface area ratio of 1.0 be used for "analytical purposes." Therefore, the overall interchange factor used for the HEATING models was 0.7347. The effect of package absorptivity, furnace emissivity, and area ratio on the thermal response of the DT-18 package is examined in detail in another report, *Effect of Gray-Body Interchange Factor and Radiating Temperature on the Thermal Response of the DT-18 Shipping Container*.⁴ A furnace radiating temperature of 800°C, also specified in 10 CFR 71, was used.

The natural convection heat transfer over the sides, top, and bottom of the package can be determined from

$$Q_{\text{conv}} = hA_{\text{package}}(T_A - T_P). \quad (4)$$

The natural convection heat transfer coefficient can be expressed as

$$h = a(T_A - T_P)^b, \quad (5)$$

where T_A is the furnace air temperature, and a and b are constants. Values for the constants, a and b , in Eq. (5) are given in Table 2 for different surface configurations. It should be noted that in the analyses the temperature of the air (T_A) is taken as the furnace surface temperature (T_F). Data consisting of control thermocouple (air) and furnace wall thermocouple temperatures support the fact that the furnace air temperature is approximately equal to the furnace wall temperatures.⁷

Since initially, temperature gradients are extremely sharp near the package surface, the mesh size used in the HEATING 7.1 models is small. The node spacing in the side model (see Fig. 2) is 1/4 in. for Region V (5 elements) and Region IV (5 elements), 1/8 in. for Region III (9 elements), and 1/16 in. for Region II (16 elements) and Region I (1 element). The side model consists of a total of 37 nodes.

The node spacing in the top model (see Fig. 2) is 1/4 in. for Region V (3 elements) and Region IV (6 elements), 1/8 in. for Region III (13 elements), and 1/16 in. for Region II (16 elements) and Region I (1 element). The top model consists of a total of 40 nodes.

The node spacing in the bottom model (see Fig. 2) is 1/4 in. for Region V (3 elements) and Region IV (10 elements), 1/8 in. for Region III (20 elements), and 1/16 in. for Region II (16 elements) and Region I (1 element). The bottom model consists of a total of 51 nodes.

The progressive mesh sizing, determined from preliminary 1-D (radial) analyses on the DT-18 package, is employed in both the r and z directions. The HEATING 7.1 input files for each of the three cases are presented in Appendices 2 through 4.

Table 2. Natural convection correlation constants

Configuration	a	b
Vertical surface	1.37	0.25
Horizontal : Hot surface facing up or cold surface facing down	1.86	0.25
Horizontal : Hot surface facing down or cold surface facing up	0.88	0.25

Source: R. H. Perry and D. W. Green, *Perry's Chemical Engineers' Handbook*, 6th ed, McGraw-Hill, New York, 1984.

DISCUSSION OF RESULTS

Plots of temperature vs depth into the Celotex™ insulating material are shown in Fig. 3 for locations corresponding to the side, top, and bottom of the DT-18 shipping package. The temperatures used to construct these plots were calculated at a time of 30 min, representing the end of the thermal test. Although the temperature of some of the Celotex™ in the package will continue to increase slowly due to conduction, it is not expected that any further charring will occur at times beyond 30 min, which corresponds to removal from the furnace. Charring depths in Fig. 3 are presented in inches since measurements were taken in these units.

As seen from Fig. 3, the temperature distributions through the insulating material at the side, top, and bottom of the DT-18 package are nearly identical. Therefore, it can be concluded that when exposed to conditions such as those specified in 10 CFR 71, uniform charring should occur around the DT-18 package. If charring begins at about 150°C as established earlier in the report, the data in Fig. 3 predict a charring depth of 1 1/8 in. This predicted charring depth agrees well with the charring depth measurements which range from an average of 3/4 to 1 1/4 in.

A plot of charring depth in the DT-18 package as a function of time is shown in Fig. 4. A temperature of 150°C was used as the charring criteria. Therefore, data points indicate that the node corresponding to the represented char depth has exceeded 150°C while the next node into the Celotex™ has a temperature below 150°C. Therefore, at 30 min the char depth at the side, top, and bottom of the DT-18 package is somewhere between 1 and 1 1/8 in. At a time of 25 min, the temperature of the side and bottom at a depth of 1 in. was slightly above 150°C, whereas the temperature of the top at a depth of 1 in. was slightly below 150°C. This explains the discrepancy in the charring depths at a time of 25 min seen in Fig. 4.

Fig. 3. Temperature of Celotex™ insulating material in the DT-18 package.

Fig. 4. Celotex™ charring depth as a function of time in the DT-18 package.

CONCLUSIONS

Based on thermal tests conducted on blocks of Celotex™ insulation, the Celotex™ charring process begins at a temperature of about 150 to 175°C.² Observation of thermally tested DT-18 packages indicates that charring is fairly uniform over the package with greater charring depths occurring near damaged or exposed areas. Measured Celotex™ charring depths ranged from approximately 1/2 to 1 1/2 in. The average charring depth observed in DT-18 packages was approximately 1 in.

HEATING 7.1 also predicts a uniform charring depth of 1 to 1 1/8 in. for the DT-18 package if charring occurs at 150°C. This seems to indicate that the charring initiation temperature of 150°C is fairly accurate. The good agreement obtained between the experimental and analytical charring depths indicates that the 1-D DT-18 models which have been developed are accurate and can be used to successfully predict charring depths in the DT-18 and in similarly constructed shipping packages. The good agreement obtained in charring depths also indicates that the thermal properties, especially those of the Celotex™ insulating material, are fairly accurate and that any changes in properties resulting from charring are not extremely significant.

REFERENCES

1. *Packaging and Transportation of Radioactive Material*, U.S. Nuclear Regulatory Commission, Title 10, Code of Federal Regulations, Part 71, Washington, D.C., 1987.
2. G. G. Chalfant, *Safety Analysis Report - Packages USA/9965-9968 (DOE-SR) (Packaging of Fissile and Other Radioactive Materials)*, DPSPU 83-124-1, 1984, p. 3-65.
3. K. W. Childs, *HEATING 7.1 User's Manual*, K/CSD/TM-96, July 1991.
4. J. C. Anderson and M. R. Feldman, *Effect of Gray-Body Interchange Factor and Radiating Temperature on the Thermal Response of the DT-18 Shipping Container*, ORNL/ENG/TM-37, March 1992.
5. J. C. Anderson, *Comparison of Experimental and Analytical Temperatures Achieved by DT-18 and PC-1 Shipping Containers During Hypothetical Thermal Accident Tests*, ORNL/ENG/TM-39, March 1992.
6. R. Siegel and J. R. Howell, *Thermal Radiation Heat Transfer*, Hemisphere Publishing Corporation, New York, 1981.
7. M. R. Feldman, *Characterization of the B-1023 Furnace for Use in Hypothetical Thermal Accident Testing of Shipping Containers in Accordance with 10 CFR, Part 71*, ORNL/ENG-10, January 1992.

Appendix 1

POST THERMAL TEST MEASUREMENTS AND OBSERVATIONS

Several DT-18 packages were opened and visually inspected for charring damage following thermal tests conducted in the B-1023 furnace at the Y-12 Plant in Oak Ridge, Tennessee. Figure A1.1 shows the location of the Celotex™ inserts in the DT-18 package. Charring depths were measured at several locations in each package. The interface between the charred and uncharred material can be easily distinguished due to the change in coloration and density (i. e., the charred material is blackened and can be easily scraped away from the undamaged Celotex™). All measurements and observations presented here were made by J. C. Anderson and J. F. DeClue.

Fig. A1.1. DT-18 Celotex™ inserts.

DT-18 UNIT A2 : POST THERMAL TEST MEASUREMENTS AND OBSERVATIONS

Date : 3/5/91

Top Insert

Overall thickness: 2 in. $< t < 2 \frac{1}{2}$ in.
Char thickness: 1 in.

Middle Insert

Overall thickness: $2 \frac{1}{2}$ in. $< t < 2 \frac{3}{4}$ in.
Char thickness: 1 in.

Notes

- Sireaking (tar) was observed on the inner container.
- Some melting of the polyurethane insulation within the inner container was observed.
- Interfaces between the char/nonchar regions had a wavy appearance in some locations.
- In a few locations, the char nearly extended through the entire insulation thickness.
- No charring was observed at Celotex™ in contact with the inner container.

DT-18 UNIT A6 : POST THERMAL TEST MEASUREMENTS AND OBSERVATIONS

Date : 4/16/91

Top Insert

Overall thickness: 2 5/8 in.
Char thickness: 1/2 in. < t < 15/16 in.

Middle Insert

Height: 6 in.
Overall thickness: 2 3/8 in. < t < 2 9/16 in.
Char thickness: 1 1/4 in. < t < 1 1/2 in.

Bottom Insert

Height: 12 in.
Overall thickness: 2 1/2 in.
Char thickness: 1 in. < t < 1 1/4 in.

Notes

- Streaking (tar) was observed on the top and on the upper half of the inner container.
- Very little streaking was observed on the lower half of the inner container.
- The lid section of the top insert was completely charred.
- No charring was observed at the Celotex™ in contact with the inner container.
- The polyurethane insulation in the inner container was not examined.

DT-18 UNIT A7 : POST THERMAL TEST MEASUREMENTS AND OBSERVATIONS

Date : 4/16/91

Top Insert

Overall thickness: 2 7/8 in.
Char thickness: 1 1/16 in. < t < 1 1/8 in.

Middle Insert

Overall thickness: 2 3/8 in. < t < 2 9/16 in.
Char thickness: 7/8 in.

Bottom Disk

Overall thickness: 5 1/2 in.
Char thickness: 1 1/16 in.

Notes

- Very little streaking (tar) was observed on the inner container.
- No charring was observed at the Celotex™ in contact with the inner container.
- The polyurethane insulation in the inner container was not examined.

Appendix 2

ONE-DIMENSIONAL DT-18 HEATING MODEL - SIDE

ONE-DIMENSIONAL DT-18 HEATING MODEL - SIDE

OPTIONS

MAXPTS=50

@MAXPBT=1

@MWIDTH=37

@MAXCP=0

DT-18 - 1-D - SIDE - WITHOUT HEAT GENERATION - 9/27/91

* SPECIFY THE CPU TIME ALLOWED, THE GEOMETRY TYPE (r), THE INITIAL

* TIME, AND THE TEMPERATURE UNITS (C)

100 4 0. 1

* DEFINE THE REGIONS

REGIONS

1 1 0.2858 0.2873 0. 0. 0. 0.

1 0 0 1 0 0 0 0

2 2 0.2604 0.2858 0. 0. 0. 0.

1 0 0 0 0 0 0 0

3 2 0.2318 0.2604 0. 0. 0. 0.

1 0 0 0 0 0 0 0

4 2 0.2032 0.2318 0. 0. 0. 0.

1 0 0 0 0 0 0 0

5 3 0.1984 0.2032 0. 0. 0. 0.

1 0 0 0 0 0 0 0

6 3 0.1778 0.1984 0. 0. 0. 0.

1 0 0 0 0 0 0 0

7 3 0.1730 0.1778 0. 0. 0. 0.

1 0 0 0 0 0 0 0

* DEFINE THE MATERIALS USED IN THE MODEL

MATERIALS

1 STEEL1 1 7900 1 -1 0 -2 0

2 CELOTEX1 1 270 1 -3 0 -4 0

3 STEEL2 1 7900 1 -1 0 -2 0

* SPECIFY THE INITIAL TEMPERATURES

INITIAL TEMPERATURES

1 21.11

* SPECIFY THE BOUNDARY CONDITIONS

BOUNDARY CONDITIONS

1 1 0.0 -5 0 0 0

0.0 4.166E-08 1.37 0.25 0.0 0

* ESTABLISH THE NODE SPACING IN THE X (r) DIRECTION

XGRID

0.1730 0.1778 0.1984 0.2032 0.2318 0.2604 0.2858 0.2873

1 3 1 5 9 16 1

TABULAR FUNCTIONS

* ENTER THE THERMAL CONDUCTIVITY DATA FOR STAINLESS STEEL

1
 -73 12.6
 @27 14.9
 @127 16.6
 @327 19.8
 @527 22.6
 @727 25.4
 @927 28.0
 * ENTER THE SPECIFIC HEAT DATA FOR STAINLESS STEEL
 2
 -73 402
 @27 477
 @127 515
 @327 557
 @527 582
 @727 611
 @927 640
 * ENTER THE THERMAL CONDUCTIVITY DATA FOR CELOTEX
 3
 25 0.053
 @86 0.059
 @146 0.063
 @226 0.065
 @278 0.051
 * ENTER THE SPECIFIC HEAT DATA FOR CELOTEX
 4
 25 1280
 @86 1506
 @146 1745
 @226 2046
 @278 2063
 * SPECIFY THE TIME DEPENDENT BOUNDARY TEMPERATURE FOR BOUNDARY
 * CONDITION #1
 5
 0.0 800
 @2100 800
 @2100.01 21.11
 * SPECIFY THE PRINTOUT TIMES
 PRINTOUT TIMES
 60 120 180 240 300 600 900 1200 1500 1800 1860 1920 1980 2040
 @2100
 TRANSIENT
 * SPECIFY THE TRANSIENT SOLUTION TECHNIQUE AND THE FINAL TIME
 1 2100
 * SPECIFY THE INITIAL TIME STEP AND THE LEVY FACTOR
 0.0 1
 %

Appendix 3

ONE-DIMENSIONAL DT-18 HEATING MODEL - TOP

ONE-DIMENSIONAL DT-18 HEATING MODEL - TOP

OPTIONS

MAXPTS=60

@MAXPBT=1

@MWIDTH=37

@MAXCP=0

DT-18 - 1-D - TOP - WITHOUT HEAT GENERATION - 10/2/91

* SPECIFY THE CPU TIME ALLOWED, THE GEOMETRY TYPE (z), THE INITIAL

* TIME, AND THE TEMPERATURE UNITS (C)

100 5 0. 1

* DEFINE THE REGIONS

REGIONS

1 1 0. 0. 0. 0. 0.7095 0.7254

1 0 0 0 0 0 0

2 2 0. 0. 0. 0. 0.7254 0.7651

1 0 0 0 0 0 0

3 2 0. 0. 0. 0. 0.7651 0.8048

1 0 0 0 0 0 0

4 2 0. 0. 0. 0. 0.8048 0.8302

1 0 0 0 0 0 0

5 3 0. 0. 0. 0. 0.8302 0.8317

1 0 0 0 0 0 1

* DEFINE THE MATERIALS USED IN THE MODEL

MATERIALS

1 STEEL1 1 7900 1 -1 0 -2 0

2 CELOTEX1 1 270 1 -3 0 -4 0

3 STEEL2 1 7900 1 -1 0 -2 0

* SPECIFY THE INITIAL TEMPERATURES

INITIAL TEMPERATURES

1 21.11

* SPECIFY THE BOUNDARY CONDITIONS

BOUNDARY CONDITIONS

1 1 0.0 -5 0 0 0

0.0 4.166E-08 0.88 0.25 0.0 0

* ESTABLISH THE NODE SPACING IN THE X (r) DIRECTION

ZGRID

0.7095 0.7254 0.7651 0.8048 0.8302 0.8317

3 6 13 16 1

TABULAR FUNCTIONS

* ENTER THE THERMAL CONDUCTIVITY DATA FOR STAINLESS STEEL

1

-73 12.6

@27 14.9

@127 16.6

@327 19.8
 @527 22.6
 @727 25.4
 @927 28.0
 * ENTER THE SPECIFIC HEAT DATA FOR STAINLESS STEEL
 2
 -73 402
 @27 477
 @127 515
 @327 557
 @527 582
 @727 611
 @927 640
 * ENTER THE THERMAL CONDUCTIVITY DATA FOR CELOTEX
 3
 25 0.053
 @86 0.059
 @146 0.063
 @226 0.065
 @278 0.051
 * ENTER THE SPECIFIC HEAT DATA FOR CELOTEX
 4
 25 1280
 @86 1506
 @146 1745
 @226 2046
 @278 2063
 * SPECIFY THE TIME DEPENDENT BOUNDARY TEMPERATURE FOR BOUNDARY
 * CONDITION #1
 5
 0.0 800
 @2100 800
 @2100.01 21.11
 * SPECIFY THE PRINTOUT TIMES
 PRINTOUT TIMES
 60 120 180 240 300 600 900 1200 1500 1800 1860 1920 1980
 @2040 2100
 TRANSIENT
 * SPECIFY THE TRANSIENT SOLUTION TECHNIQUE AND THE FINAL TIME
 1 2100
 * SPECIFY THE INITIAL TIME STEP AND THE LEVY FACTOR
 0.0 1
 %

Appendix 4

ONE-DIMENSIONAL DT-18 HEATING MODEL - BOTTOM

ONE-DIMENSIONAL DT-18 HEATING MODEL - BOTTOM

OPTIONS

MAXPTS=60

@MAXPBT=1

@MWIDTH=37

@MAXCP=0

DT-18 - 1-D - BOTTOM - WITHOUT HEAT GENERATION - 10/2/91

* SPECIFY THE CPU TIME ALLOWED, THE GEOMETRY TYPE (z), THE INITIAL

* TIME, AND THE TEMPERATURE UNITS (C)

100 5 0. 1

* DEFINE THE REGIONS

REGIONS

1 1 0. 0. 0. 0. 0. 0.0015

1 0 0 0 0 1 0

2 2 0. 0. 0. 0. 0.0015 0.0269

1 0 0 0 0 0 0

3 2 0. 0. 0. 0. 0.0269 0.0904

1 0 0 0 0 0 0

4 2 0. 0. 0. 0. 0.0904 0.1539

1 0 0 0 0 0 0

5 3 0. 0. 0. 0. 0.1539 0.1698

1 0 0 0 0 0 0

* DEFINE THE MATERIALS USED IN THE MODEL

MATERIALS

1 STEEL1 1 7900 1 -1 0 -2 0

2 CELOTEX1 1 270 1 -3 0 -4 0

3 STEEL2 1 7900 1 -1 0 -2 0

* SPECIFY THE INITIAL TEMPERATURES

INITIAL TEMPERATURES

1 21.11

* SPECIFY THE BOUNDARY CONDITIONS

BOUNDARY CONDITIONS

1 1 0.0 -5 0 0 0

0.0 4.166E-08 1.86 0.25 0.0 0

* ESTABLISH THE NODE SPACING IN THE X (r) DIRECTION

ZGRID

0. 0.0015 0.0269 0.0904 0.1539 0.1698

1 16 20 10 3

TABULAR FUNCTIONS

* ENTER THE THERMAL CONDUCTIVITY DATA FOR STAINLESS STEEL

1

-73 12.6

@27 14.9

@127 16.6

@327 19.8
 @527 22.6
 @727 25.4
 @927 28.0
 * ENTER THE SPECIFIC HEAT DATA FOR STAINLESS STEEL
 2
 -73 402
 @27 477
 @127 515
 @327 557
 @527 582
 @727 611
 @927 640
 * ENTER THE THERMAL CONDUCTIVITY DATA FOR CELOTEX
 3
 25 0.053
 @86 0.059
 @146 0.063
 @226 0.065
 @278 0.051
 * ENTER THE SPECIFIC HEAT DATA FOR CELOTEX
 4
 25 1280
 @86 1506
 @146 1745
 @226 2046
 @278 2063
 * SPECIFY THE TIME DEPENDENT BOUNDARY TEMPERATURE FOR BOUNDARY
 * CONDITION #1
 5
 0.0 800
 @2100 800
 @2100.000001 21.11
 * SPECIFY THE PRINTOUT TIMES
 PRINTOUT TIMES
 60 120 180 240 300 600 900 1200 1500 1800 1860 1920 1980
 @2040 2100
 TRANSIENT
 * SPECIFY THE TRANSIENT SOLUTION TECHNIQUE AND THE FINAL TIME
 1 2100
 * SPECIFY THE INITIAL TIME STEP AND THE LEVY FACTOR
 0.0 1
 %

INTERNAL DISTRIBUTION

1-5.	J. C. Anderson	22.	R. D. Poor
6.	H. C. Beeson	23.	J. C. Salyers
7.	J. P. Belk	24.	W. C. Stoddart
8.	R. W. Bleniek	25.	E. Stumpfl
9.	B. B. Bowden	26.	A. J. Szady, Jr.
10.	J. F. DeClue	27.	P. A. Tabor
11.	J. R. Dixon	28.	D. A. Tollefson
12.	D. A. Dyslin	29.	M. S. Walker
13.	B. F. Elam	30.	J. C. Walls
14.	M. R. Feldman	31.	D. E. Welch
15.	C. P. Frew	32.	W. R. Williams
16.	R. W. Glass	33-34.	Central Research Library
17.	R. F. Holdaway	35.	Y-12 Technical Reference Section
18.	K. G. Kahl	36.	Y-12 Plant Records
19.	C. D. Liles	37.	Laboratory Records
20.	S. D. Moses	38.	Laboratory Records - Record Copy
21.	W. O. Nobles	39.	ORNL Patent Section

EXTERNAL DISTRIBUTION

- 40. Assistant manager for Energy Research and Development, DOE-OR, P.O. Box 2001, Oak Ridge, TN 37831-8600
- 41. Frank Punch, U.S. Department of Energy, EH-33.3 GTN, Washington, D.C. 20585
- 42. Roger W. Carlson, Lawrence Livermore National Laboratory, P. O. Box 808, Mail Code L-197, Livermore, CA 94551
- 43. Larry E. Fischer, Lawrence Livermore National Laboratory, P. O. Box 808, Mail Code L-197, Livermore, CA 94551
- 44. James H. VanSant, Lawrence Livermore National Laboratory, P. O. Box 808, Mail Code L-197, Livermore, CA 94551
- 45-56. Office of Scientific and Technical Information, Bldg. 1916-T1, Oak Ridge Turnpike, Oak Ridge, TN 37830

**DATE
FILMED**
7/17/92