"Design, Synthesis, and Characterization of Novel Fine-Particle, Unsupported Catalysts for Coal Liquefaction"

DRAFT
Technical Progress Report

Year One
10/25/90-10/24/91

Michael T. Klein
Principal Investigator

Center for Catalytic Science and Technology
Department of Chemical Engineering
University of Delaware
Newark, Delaware 19716

Date Published:
December 30, 1991

Contract Number: DE-AC22-90PC90050

Prepared for Department of Energy

U. S. DOE PATENT CLEARANCE IS NOT REQUIRED PRIOR
TO PUBLICATION OF THIS DOCUMENT

MASTER

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

js

INTRODUCTION

The purpose of this work is to investigate the kinetics-assisted design, synthesis and characterization of fine-particle, unsupported catalysts for coal liquefaction. The goal is to develop a fundamental understanding of coal catalysis and catalysts that will, in turn, allow for the specification of a novel optimal catalyst for coal liquefaction.

EXECUTIVE SUMMARY

The first task in the project is to study ultrafine dispersions of metal sulfides for hydrogenation, hydrogenolysis, and hydrocracking. In this regard, a series of substituted iron carbonyls has been prepared which decompose thermally or photochemically in the presence of sulfur compounds to give finely divided iron sulfides. The modifications made to the iron carbonyls are intended to elucidate the effects of such properties as thermal stability, presence of readily available coordinated sulfur, and presence of metal-metal bonds. These compounds are being investigated to determine if and how the substitutions affect their performance as coal liquefaction catalysts or catalyst precursors. Also, colloidal iron systems are being studied as a source of ultrafine particle catalysts. These have been prepared by decomposition of iron pentacarbonyl in reverse-micelle systems, and evaluation of the catalytic performance of these systems will soon be underway.

Tubing Bomb reactors are being employed to characterize the activity of catalysts through kinetic analysis. A coal model compound, dibenzyl ether (DBE), is being used to characterize the catalyst precursors. Testing conditions have been established at which kinetic data may be accurately extracted for the DBE system. Some kinetic data has been collected for the $\text{Fe}(\text{CO})_4\text{PPh}_3$ catalyst precursor which shows first order disappearance of DBE up to 120 minutes at 250°C and marked catalyst deactivation after 120 minutes.

In addition, a catalytic coal liquefaction experiment ($\text{Fe}(\text{CO})_5$ as the catalyst precursor at 388°C) has been performed in a novel short contact time flow reactor using Illinois #6 coal. The results of this experiment will be compared to thermal coal liquefaction results which have already been obtained in this novel reactor.

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

I. CATALYST SYNTHESIS / CHARACTERIZATION

The concept behind our approach to catalytic coal liquefaction is that homogeneous or small catalyst particles are able to penetrate the coal structure during early stages of liquefaction and direct the dissolution of the coal from within. The ability of the catalyst to penetrate into coal is important, since the three-dimensional, macromolecular solid nature of coal limits the contact between coal and a more traditional, large-particle catalyst. Ultrafine particle catalysts thus offer increased surface area and improved coal-catalyst contacting.

The first task in our study of catalysts for coal liquefaction was to prepare ultrafine dispersed catalysts to carry out hydrogenation and hydrogenolysis reactions. Four classes of materials were chosen for investigation:

- metal carbonyls
- substituted carbonyls
- single-metal and mixed-metal carbonyl clusters
- metal sulfides

A. SUBSTITUTED IRON CARBONYL COMPOUNDS

Iron pentacarbonyl ($\text{Fe}(\text{CO})_5$) was chosen as the starting point for this investigation for several reasons. $\text{Fe}(\text{CO})_5$ has been shown previously by several researchers to be an effective coal liquefaction catalyst^{1,2}. It is a fairly well-studied catalyst, and thus previous work can provide a baseline for the present work. Also, there is a wide range of synthetic chemistry routes available to the iron carbonyls, which should make them good precursors for homogeneous or heterogeneous catalysts.

Our initial objectives were to prepare a series of substituted iron carbonyl compounds and then determine if and how the modifications affect their catalytic performance (compared to the base case, $\text{Fe}(\text{CO})_5$).

Thermal Stability

Under coal liquefaction conditions, $\text{Fe}(\text{CO})_5$ is thermally unstable, being converted to catalytically active iron pyrrhotite (Fe_{1-x}S) in the presence of sulfur². Because of its poor thermal stability and consequent breakdown to a different, more active species, $\text{Fe}(\text{CO})_5$

would be considered a catalyst precursor, rather than a homogeneous catalyst. To consider the effect thermal stability has on the activity of iron carbonyl as a homogeneous catalyst, triphenylphosphine ligands (PPh₃) were introduced into the iron coordination sphere in the preparation of the following two compounds:

Fe(CO)₄PPh₃

Fe(CO)₃(PPh₃)₂

The thermal stability of these compounds increases in the order Fe(CO)₅ < Fe(CO)₄PPh₃ < Fe(CO)₃(PPh₃)₂.

Fe(CO)₄PPh₃ was prepared by a combined photochemical and thermal route from triphenylphosphine (PPh₃) in iron pentacarbonyl (Fe(CO)₅), following the synthesis procedure of Conder and Darensbourg³. This preparation procedure, which is selective to the monosubstituted product, is outlined below:

Thus 3 g of PPh₃ (0.011 mole) was added to 28 ml of Fe(CO)₅ (0.208 mole) under a dry N₂ atmosphere. The stirred solution was irradiated with a 100-Watt long-wave UV lamp for 2 hours. The lamp was then turned off and the solution was held at reflux conditions (100°C) for 1 hour, followed by an additional hour of reflux with the UV lamp turned back on. At the end of the reaction sequence, excess Fe(CO)₅ was removed in vacuo. The residue was extracted with 50 ml THF and chromatographed on a neutral alumina column, eluting with 75 ml THF. 50 ml of distilled water was then added and the solution volume reduced under vacuum to precipitate pale yellow crystals which were collected by filtration

and purified by recrystallization from heptane. The above procedure gave a 50% yield of $\text{Fe}(\text{CO})_4\text{PPh}_3$ (based on PPh_3).

$\text{Fe}(\text{CO})_3(\text{PPh}_3)_2$ was prepared from $\text{Fe}(\text{CO})_5$ and PPh_3 in refluxing cyclohexanol, following the procedure of Clifford and Mukherjee⁴:

In this synthesis, 2 ml of $\text{Fe}(\text{CO})_5$ (0.015 mole) and 5 g of PPh_3 (0.018 mole) were added to 100 ml of cyclohexanol which had been distilled under N_2 over 4Å molecular sieve to remove oxygen and water. The solution was then refluxed (161°C) for 1 hour under N_2 . 100 ml of hexane was added to the reaction solution which was then cooled, giving a yellow precipitate. This relatively straightforward procedure gave a 39% yield (based on $\text{Fe}(\text{CO})_5$) of the disubstituted product, $\text{Fe}(\text{CO})_3(\text{PPh}_3)_2$, with a small amount of the monosubstituted derivative, $\text{Fe}(\text{CO})_4\text{PPh}_3$, present.

Coordinated Sulfur. Metal-Sulfur Clusters

Because of the recognized catalytic activity of iron sulfides for coal liquefaction, the following iron carbonyl compounds (containing coordinated sulfur) were prepared:

$\text{Fe}(\text{CO})_2(\text{PPh}_3)_2\text{CS}_2$ was prepared from diiron nonacarbonyl ($\text{Fe}_2(\text{CO})_9$) and PPh_3 in refluxing (46°C) carbon disulfide (CS_2), as outlined by Baird et al.⁵:

A mixture of 1.5 g of $\text{Fe}_2(\text{CO})_9$ (0.004 mole) and 3 g of PPh_3 (0.011 mole) in 25 ml of CS_2 was refluxed under N_2 for 40 minutes. The solution was cooled, and the rust-red solid, $\text{Fe}(\text{CO})_2(\text{PPh}_3)_2\text{CS}_2$, was precipitated by addition of diethylether (~5-10% yield based on $\text{Fe}_2(\text{CO})_9$).

$\text{S}_2\text{Fe}_2(\text{CO})_6$ and $\text{S}_2\text{Fe}_3(\text{CO})_9$ were prepared from $\text{Fe}(\text{CO})_5$ and Na_2S_5 , as described by Seyferth et al.⁶:

In this procedure, 8 ml of $\text{Fe}(\text{CO})_5$ (0.06 mole) and 16 ml of 50% aqueous KOH (w/v) were added to 40 ml of degassed methanol at 0°C . An aqueous solution equivalent to 83 mmol of Na_2S_5 was then added, and the mixture was stirred at 0°C for 2 hours. The reaction mixture was then acidified by slow addition of 80 ml of degassed 18.5% HCl solution which gave a brown precipitate. The brown precipitate was collected by filtration and twice extracted with pentane. The pentane was then removed in vacuo to give a reddish-brown solid. Sublimation of the solid at 40.5°C for 10 hours yielded dark ruby-red crystals of $\text{S}_2\text{Fe}_2(\text{CO})_6$ (5% yield based on $\text{Fe}(\text{CO})_5$). The remaining solid ($\text{S}_2\text{Fe}_3(\text{CO})_9$ and decomposition products) was dissolved in 50 ml pentane and passed through a 4 cm bed of silica gel in a filter funnel to remove decomposition products. Subsequent pentane removal (in vacuo) gave brown $\text{S}_2\text{Fe}_3(\text{CO})_9$ at a yield of 7% (based on $\text{Fe}(\text{CO})_5$).

Characterization

Identification of all of the above compounds was made by comparison of their color, infrared spectra, and melting points with literature values, as shown in Table I.

Table I

Compound	Medium	CO stretch (cm ⁻¹)			Melt Pt.(°C)
Fe(CO) ₄ PPh ₃	CH ₂ Cl ₂	2051	1974	1939	198-200
	CHCl ₃ ⁷	2059	1978	1938	201-203
Fe(CO) ₃ (PPh ₃) ₂	CH ₂ Cl ₂	1882			265-285
	CHCl ₃ ⁷	1887			272
Fe(CO) ₂ (PPh ₃) ₂ CS ₂	CH ₂ Cl ₂	1990	1929		133
	CH ₂ Cl ₂ ⁵	1989	1929		130-134
S ₂ Fe ₂ (CO) ₆	CH ₂ Cl ₂	2083	2042	2003	-
	CCl ₄ ⁸	2081	2042	2005	45-46
S ₂ Fe ₃ (CO) ₉	CCl ₄	2063	2043	2020	113
	CCl ₄ ⁸	2063	2045	2024	114

Having prepared the above compounds, the next objective was to investigate their catalytic performance for hydrogenation and hydrogenolysis reactions, and to thereby determine the effects of thermal stability, coordinated sulfur, and metal-metal bonds on catalyst activity. Results thus far indicate that all the compounds prepared as described above are unstable at liquefaction conditions, and thus might better be termed catalyst precursors. The primary method used to characterize catalyst performance thus far has been tubing bomb reactor test results (*vide infra*). Other characterization tools in use are bench-top glass reactor model compound tests and decomposition studies, scanning and transmission electron microscopy, and IR spectroscopy. A diagram of the bench-top glass reactor is shown in

Figure 1. The reactor is equipped with a thermometer, N₂ purge lines, a water-cooled reflux condenser, a septum port for syringe sampling, and a powder addition funnel for catalyst addition. Designed as a supplement to tubing bomb reactor tests, this test reactor allows the reactant/solvent system to be heated to reaction temperature prior to catalyst addition, providing isothermal conditions throughout the course of a test. Also, liquid samples can be drawn during the test, and reaction products can be removed and isolated after a test in an air-free environment. The glass reactor also allows visual observation of changes that occur during reaction (such as catalyst decomposition).

FIGURE 1: Bench-top glass reactor for model compound tests and decomposition studies. It is equipped with a thermometer, N₂ purge lines, a water-cooled reflux condenser, a septum port for sampling, and a powder addition funnel for catalyst addition.

In the first glass reactor run, dibenzyl ether was chosen as the coal model compound, and 1-methylnaphthalene (bp 240-243°C) was used as a non-hydrogen-donor solvent. The glass reactor was charged with 15 g of dibenzyl ether, 45 g of 1-methylnaphthalene, and 0.75 ml of carbon disulfide (CS₂). Under a N₂ atmosphere, the reaction solution was heated to reflux temperature (240.5°C), at which point 0.75 g of the catalyst precursor Fe(CO)₂(PPh₃)₂CS₂ and 0.64 g of triphenylphosphine was added to the reaction mixture. Upon addition to the hot solvent/substrate, the precursor decomposed rapidly to give a fine

black precipitate. Samples of the reaction mixture were then drawn at 10 minute intervals for 1 hour. Upon GC analysis of these samples, however, no appreciable reaction was observed after 1 hour at the reflux temperature (240.5°C). The precipitate was examined by SEM/EDAX, which showed ~1 micron particles of fairly uniform size and composition containing iron and sulfur. Future glass reactor test runs are planned at higher temperatures (obtained by using higher-boiling solvents) and longer reaction times, using different model compounds.

B. HETEROGENEOUS CATALYSTS

Up until this point, homogeneous, or molecular, species have been prepared for use as homogeneous and heterogeneous catalysts. Our investigation next turned towards preparation of heterogeneous materials designed to function as heterogeneous catalysts. Work by Hess and Parker⁹ has shown that uniformly sized, stable colloidal metal particles can be prepared by thermal decomposition of metal carbonyls in the presence of a surfactant. In light of this work, a study of the use of colloidal ultrafine particle iron as a coal liquefaction catalyst has been initiated. The general synthesis route is as follows:

The resulting particles are generally on the order of 5-20 nm, and are highly monodisperse ($\sigma \sim 1$ nm). Some of the possible advantages of the metal carbonyl synthesis route to colloidal metal particles are:

- Photochemical (low temperature) synthesis
- True fine-particle metal alloys via mixed-metal carbonyls
- Colloidal metal sulfides by:
 - Sulfur-containing carbonyl precursors
 - Addition of sulfur source during synthesis
 - Sulfiding metal particles after synthesis

Five colloidal iron systems have been prepared at this point. The basic synthesis procedure followed is outlined below¹⁰:

In the first synthesis (S-21), 4.27 g of the surfactant, n-oleoylsarcosine and 27.7 g of Fe(CO)_5 (12:1 molar ratio of Fe(CO)_5 to surfactant) were added to 100 ml of Decalin (distilled under N_2 over 4Å molecular sieve to remove oxygen and water). This solution was then heated to reflux for approximately ten hours, over which time the reflux temperature increased from 120°C to 189°C as the Fe(CO)_5 decomposed. The resulting mixture was targeted to contain 9 wt% Fe. TEM inspection indicated this mixture consisted of colloidal particles 8-10 nm in size. Syntheses S-24 and S-26 followed the procedure outlined above, but with lower surfactant loadings (24:1 and 48:1 molar ratio of Fe(CO)_5 to surfactant, respectively), to investigate whether some size control could be achieved. TEM analysis of the mixtures thus prepared has not been completed yet.

In an attempt to prepare colloidal iron sulfide, synthesis S-22 followed the procedure outlined for S-21 with a sulfur source, diphenyldisulfide ($(\text{C}_6\text{H}_5\text{S})_2$), added prior to heating to reflux. The success of the synthesis was mixed, as both colloidal and larger precipitated particles formed, the compositions of which have not yet been determined.

An attempt has also been made to prepare colloidal iron particles by photochemical decomposition of Fe(CO)_5 . Synthesis S-25 followed the same procedure as S-24, with the reflux period replaced by 48 hours of irradiation by a 100-Watt long-wave UV lamp. This resulted in a mixture which appeared to be colloidal. After retaining a sample, the remaining solution was heated to reflux for 3 hours to ensure complete decomposition of the Fe(CO)_5 . Characterization of the solutions before and after the final heat-up has yet to be completed.

After characterization, these colloidal metal particles will be tested with coal/coke model compounds in tubing bomb or bench-top glass reactors.

C. FUTURE WORK

Recognizing that different conditions may be optimal for activating catalysts versus liquefying coal, we plan to investigate optimizing the decomposition, or "activation", conditions for converting the iron-carbonyl based precursors to an active catalytic species.

With regard to colloidal metal systems, we plan to confirm a preparation procedure for iron sulfide ultrafine particle systems and for ultrafine particle mixed-metal alloys and sulfides. These will then be tested with model compounds and coal to determine their catalytic activity.

Also, we plan to begin synthesis of ferredoxin analogs. Ferredoxin analogs are self-assembling Fe-S clusters which model iron-sulfur protein (ferredoxin) active sites. They have been shown to be active in oxidation/reduction reactions. Their structures include those with the general formula $[\text{Fe}_4\text{S}_4(\text{SR})_4]^{2-}$:

These will be investigated as possible catalysts or catalyst precursors for direct coal liquefaction.

II. KINETIC CHARACTERIZATION

A. EQUIPMENT

To investigate short contact time catalytic coal liquefaction, our initial efforts focused on the pyrolysis and catalyzed reactions of coal and a model compound, dibenzyl ether (DBE). The batch reactors which are being employed for this work are shaker tubing bomb reactors. The shaker tubing bomb reactors have a volume of 12 mL and are connected to an agitator which can shake the bombs vertically during reaction in the fluidized sand bath. Moreover, the shaker tubing bombs are fitted with Swagelok™ tubing and valves which allow the reactors to be pressurized with nitrogen or hydrogen gases as well as allow the collection of gas samples (See Figure 2).

FIGURE 2: Shaker Tubing Bomb: Charged with Reactant, Tetralin, and 1/2" stainless steel ball bearing (for agitation), plunged into 400°C fluidized sand bath, and shaken vertically at approximately two cycles/second. Assumed heat up time was four minutes.

B. BATCH EXPERIMENTS

Reactions were performed in the shaker tubing bombs at 400 °C with a loading of 1 g Illinois #6 coal and 3 g tetralin. Initial results of these noncatalytic coal liquefaction trials are shown in Figure 3. Data points taken at 3 and 5 minutes show lower conversions than do the other data. These lower conversions correspond to the values reported by Neavel¹¹ for coal liquefaction in a non-donor vehicle. Moreover, the higher conversion data correspond to Neavel's results for liquefaction in a hydrogen donor vehicle. Therefore, our results suggest that the powdered coal samples (~ 100 mesh) are not consistently mixing with the donor solvent (Tetralin). Changes in the experimental procedure have been implemented to eliminate these transport limitations.

**CONVERSION OF COAL IN TETRALIN WITH TIME AT 400°C
IN A SHAKER TUBING BOMB REACTOR**

FIGURE 3: Coal Conversion: Mass Conversion of Illinois #6 coal to Methylene Chloride solubles on a mass ash free basis. These conversions were calculated using a low temperature ash technique. The data points at 3 and 5 min. show transport limitations.

In addition, the model compound dibenzyl ether (DBE) was used for testing the catalysts. The initial experiments were performed with a loading of 1 g DBE, 3 g Tetralin, 50 mL CS₂ and approximately 0.1 g catalyst precursor (prepared from Fe(CO)₅ and CS₂) at 400 °C. These experiments showed that with a 1 minute reaction time (after heat up) 100% of the

DBE had been converted. Milder conditions were sought out in order to measure the kinetics of the DBE reactions. Additional runs reacting the same loadings but with approximately 20 - 30 mg of the $\text{Fe}(\text{CO})_5$ and CS_2 catalyst were performed at the milder conditions of 345°C under atmospheric pressure of Nitrogen. Again, the reaction of DBE to toluene and benzaldehyde went to completion at short times and kinetic data could not be extracted from the experiment.

A similar experiment was performed using a different catalyst at the same conditions. The catalyst used in this case was an AmocatTM catalyst, received courtesy of the Amoco Oil Company. This catalyst is Nickel-Molybdenum on Alumina which has been optimized for coal liquefaction. It is used as a reference catalyst for coal liquefaction research at Amoco, and we will be using it in a similar manner in our research. Approximately 100 mg of the AmocatTM (NiMo) catalyst was reacted in Tubing Bombs with 1g of DBE in an excess of Tetralin at 345°C under atmospheric pressure of Nitrogen. The results obtained were similar to those with the $\text{Fe}(\text{CO})_5$ and CS_2 catalyst. The reaction proceeded to completion and no kinetic data could be extracted. Runs at a milder temperature of 275°C under 1 atmosphere pressure of Nitrogen were the next set of experiments attempted. Under these conditions our reaction times ran from approximately 5 to 10 minutes. (including heat up time). An experiment using approximately 100 mg of crushed AmocatTM (NiMo) catalyst was performed at these conditions, and a first order rate law was calculated from the data (See Figure 4), and the rate constant was found to be $3.93 (\text{min} \cdot \text{g catalyst})^{-1}$.

**FIRST ORDER RATE LAW FOR AMOCAT CATALYST
WITH DBE IN AN EXCESS OF TETRALIN, 275°C**

FIGURE 4: Pseudo-first order rate law fit for DBE in Tetralin with Amocat™ (NiMo) catalyst. Performed in Tubing Bomb Reactors at 275°C under 1 atmosphere of Nitrogen. $k = 3.93 \text{ (min} \cdot \text{g catalyst)}^{-1}$.

A similar experiment using approximately 50 mg of $\text{Fe}(\text{CO})_3(\text{PPh}_3)_2$ as the catalyst precursor at the same conditions also yielded a first order rate law (See Figure 5). The rate constant in this case was found to be $1.89 \text{ (min} \cdot \text{g catalyst)}^{-1}$.

FIRST ORDER RATE LAW FOR $\text{Fe}(\text{CO})_4\text{PPh}_3$ AND $\text{Fe}(\text{CO})_3(\text{PPh}_3)_2$ CATALYST WITH DBE IN AN EXCESS OF TETRALIN, 275°C

FIGURE 5 Pseudo-first order rate law fit for DBE in Tetralin with $\text{Fe}(\text{CO})_4\text{PPh}_3$ and $\text{Fe}(\text{CO})_3(\text{PPh}_3)_2$ as catalyst. Performed in Tubing Bomb Reactors at 275°C under 1 atmosphere of Nitrogen. $k = 1.89 (\text{min} \cdot \text{g catalyst})^{-1}$.

The $\text{Fe}(\text{CO})_2(\text{PPh}_3)_2\text{CS}_2$ catalyst showed a remarkably higher activity for cracking the DBE than did the other Iron based and Amocat™ catalysts. In all of the cases, the same major products were identified: benzaldehyde, benzyl alcohol and toluene. A summary of the kinetic results found at the 275°C conditions is listed in Table II and shown graphically in Figure 6.

CATALYST	1ST ORDER RATE CONSTANT AT 275°C (MIN ⁻¹ g CATALYST ⁻¹)	
	Atmospheric Nitrogen 50 µL Carbon Disulfide	Atmospheric Nitrogen 50 µL Carbon Disulfide Excess of PPh ₃
Amocat™ NiMo / Alumina	3.92	
Fe(CO) ₃ (PPh ₃) ₂	1.89	8.22
Fe(CO) ₄ (PPh ₃)	5.28	
Fe(CO) ₂ (PPh ₃) ₂ CS ₂		78.01
NONE		No Reaction at 8 min

Table II: Pseudo first-order rate constants for DBE in the presence of various catalysts.

First Order Rate Laws for the Disappearance of DBE

Figure 6: Pseudo-first order rate constants for the catalytic cracking of DBE at 275°C in an excess of Tetralin. The catalysts used were Amocat™ (NiMo / Al₂O₃), Fe(CO)₃(PPh₃)₂, and Fe(CO)₂(PPh₃)₂CS₂. The values of the rate constant were 3.92, 8.22, and 78.01 (min*g cat.)⁻¹ respectively. All three of the catalysts were run in an excess of CS₂ and the Fe(CO)₃(PPh₃)₂ and Fe(CO)₂(PPh₃)₂CS₂ catalysts were run in an excess of PPh₃.

Two additional Iron Carbonyl based catalyst precursors containing multiple iron atoms and sulfur were synthesized and tested in this same system. Their activities were found to be well above the thermal baseline, but lower than the original three Iron Carbonyl catalyst precursors and Amocat™. The first order rate constants for these new catalysts are summarized in Table III.

TABLE III

<u>Catalyst/Precursor</u>	<u>1st Order Rate Constant (min*g cat.)⁻¹</u>
Fe ₂ S ₂ (CO) ₆	0.73
Fe ₃ S ₂ (CO) ₉	0.85

Our next task was to lower the temperature of the reaction conditions even further in order to increase reaction times and improve the reliability of our kinetic data. Reactions similar to those run at 275°C are being performed at 250°C where the reaction times range from 1 to 5 hours. In addition, we are performing these experiments to elucidate the effect of the concentration of the sulfur source (CS₂) on the kinetics of the catalyzed DBE reaction. To this end, a series of experiments was planned in which the amount of CS₂ loaded into the reactor was to be varied from none to 250μL, holding all other variables constant (1g DBE, 3g Tetralin, 0.025g Fe(CO)₄PPh₃, and 0.02g PPh₃). Some of these experiments have been performed and analyzed. The results are shown in Figure 7.

FIGURE 7: Disappearance of dibenzyl ether with time at 250°C under the standard testing conditions as measured in tubing bomb batch reactors.

The plot of $\ln[\text{DBE}]/[\text{DBE}_0]$ versus Time*g. catalyst shows first order kinetics for the first 120 minutes and then a sharp deactivation of the catalyst, after which it appears that no more of the DBE is converted. The first order rate constant fitted to the <120 minute data is $0.685 \text{ (min} \cdot \text{g cat.)}^{-1}$. Similar shaker tubing bomb experiments are planned with the other catalyst precursors.

C. SHORT CONTACT TIME CSTR EXPERIMENTS

In addition to the initial shaker tubing bomb thermal coal liquefaction experiment that was described earlier, an experiment using a Pulse-Injection Flow Reactor has also been performed. The experiment was carried out using a 50 g charge of Illinois #6 coal and 2 g of a liquid catalyst, $\text{Fe}(\text{CO})_5$, in an excess of Tetralin. The flow of Tetralin was 7 L/hr under a 850 psig Nitrogen atmosphere and the experiment was carried out isothermally at approximately 388°C. The analytical chemistry to characterize the catalytic liquefaction is underway, and we plan to compare the results of the catalytic run to those of previously performed non-catalytic coal liquefactions from the same reactor.

D. FUTURE WORK

In future work, we plan to continue performing DBE experiments in shaker tubing bomb reactors to finish our analysis of the sulfur effects at 250°C. We will also perform the batch experiments with other model compounds to investigate other chemistries relevant to coal liquefaction (*i.e.* Tetralin dehydrogenation for hydrogenation activity and 1,3 biphenyl propane cracking for carbon-carbon bond scission activity).

In addition we will continue the analytical work on the catalytic Illinois#6 coal liquefaction experiment. We will also perform a thermal liquefaction using the Pulse-Injection CSTR Flow reactor on the DOE coal Bank DECS-17 (Blind Canyon Seam) coal sample to lay the groundwork for future catalytic coal liquefaction experiments.

REFERENCES

1. Watanabe, Y., Yamada, O., Fujita, K., Takegami, Y., and Suzuki, T., "Coal Liquefaction using Iron Complexes as Catalysts", *Fuel*, 1984, **63**, 752-755.
2. Herrick, D.E., Tierney, J.W., and Wender, I., "Activity and Characterization of Coprocessing Catalysts Produced from an Iron Pentacarbonyl Precursor", *Energy & Fuels*, 1990, **4**, 231-236.
3. Conder, H.L., and Darensbourg, M. York, "The Synthesis of Group V Substituted Derivatives of Iron Pentacarbonyl in High Yield", *J. Organomet. Chem.*, 1974, **67**, 93-97.

4. Clifford, A.F., and Mukherjee, A.K., "Iron Carbonyl Complexes of Triphenylphosphine, Triphenylarsine, and Triphenylstibine", *Inorg. Chem.*, 1963, 2, No. 1, 151-153.
5. Baird, M.C., Hartwell, jun., G., and Wilkinson, G., "Carbon Disulphide Complexes of Vanadium, Iron, Cobalt, Ruthenium, and Iridium; the Preparation of trans-Bis(triphenylphosphine)thiocarbonylhalogeno-rhodium(I) and -rhodium(III) Complexes", *J. Chem. Soc. (A)*, 1967, 2037-2040.
6. Seyferth, D., Henderson, R.S., and Song, L., "Chemistry of m-Dithio-bis(tricarbonyliron), a Mimic of Inorganic Disulfides. 1. Formation of Di-m-thiolato-bis(tricarbonyliron) Dianion", *Organometallics*, 1982, 1, 125-133.
7. Cotton, F.A. and Parish, R.V., "The Stereochemistry of Five-coordinate Compounds. Part I. Infrared Spectra of Some Iron(0) Compounds", *J. Chem. Soc.*, 1960, 1440-1446.
8. Hieber, W. and Gruber, J.Z., "Zur Kenntnis der Eisencarbonylchalkogenide", *Z. Anorg. Allg. Chem.*, 1958, 91-103.
9. Hess, P.H., and Parker, Jr., P.H., "Polymers for Stabilization of Colloidal Cobalt Particles", *Journal of Applied Polymer Science*, 1966, 10, 1915-1927.
10. van Wazer, J., Mørup, S., Charles, S.W., Wells, S., and Villadsen, J., "Formation of a Metallic Glass by Thermal Decomposition of $\text{Fe}(\text{CO})_5$ ", *Physical Review Letters*, 1985, vol. 55, no. 4, 410-413.
11. Neavel, R.C., "Liquefaction of Coal in Hydrogen-donor and Non-donor Vehicles", *Fuel*, 1976, 55, 237-242.

END

**DATE
FILMED
8 / 19 / 92**