QUARTERLY TECHNICAL PROGRESS REPORT 3
APRIL - JUNE, 1987

ENHANCED DURABILITY AND REACTIVITY FOR
ZINC FERRITE DESULFURIZATION SORBENT

By

Mahesh C. Jha

Linda K. Baltich

Mark H. Berggren

AMAX Research & Development Center

5950 McIntyre Street

Golden, Colorado 80403-7499

Prepared for

U. S. Department of Energy

Morgantown Energy Technology Center

P. O. Box 880

3610 Collins Ferry Road

Morgantown, West Virginia 26507-0880

DOE Contract No. DE-AC21-86MC23172

AMAX Project No. 80270

August 28, 1987

AMAX

Research & Development Center

5950 McIntyre Street • Golden, Colorado 80403-7499

DATE 7/28/92

LEGAL NOTICE

THIS REPORT WAS PREPARED BY AMAX RESEARCH & DEVELOPMENT CENTER, AS AN ACCOUNT OF WORK SPONSORED BY MORGANTOWN ENERGY TECHNOLOGY CENTER. NEITHER AMAX RESEARCH & DEVELOPMENT CENTER NOR ANY PERSON ACTING ON ITS BEHALF:

- (A) MAKES ANY WARRANTY, EXPRESSED OR IMPLIED, WITH RESPECT TO THE USE OF ANY INFORMATION, APPARATUS, METHOD, OR PROCESS DISCLOSED IN THIS REPORT OR THAT SUCH USE MAY NOT INFRINGE PRIVATELY OWNED RIGHTS; OR
- (B) ASSUMES ANY LIABILITIES WITH RESPECT TO THE USE OF, OR FOR THE DAMAGES RESULTING FROM THE USE OF, ANY INFORMATION, APPARATUS, METHOD, OR PROCESS DISCLOSED IN THIS REPORT.

DOE/MC/23172--T13

DE92 017769

QUARTERLY TECHNICAL PROGRESS REPORT 3
APRIL - JUNE, 1987

ENHANCED DURABILITY AND REACTIVITY FOR
ZINC FERRITE DESULFURIZATION SORBENT

By
Mahesh C. Jha
Linda K. Baltich
Mark H. Berggren
AMAX Research & Development Center
5950 McIntyre Street
Golden, Colorado 80403-7499

Prepared for
U. S. Department of Energy
Morgantown Energy Technology Center
P. O. Box 880
3610 Collins Ferry Road
Morgantown, West Virginia 26507-0880

DOE Contract No. DE-AC21-86MC23172
AMAX Project No. 80270

August 28, 1987

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

MASTER

26

TABLE OF CONTENTS

	<u>Page</u>
SUMMARY	1
INTRODUCTION	2
ACCOMPLISHMENTS	3
TASK 1. EXPERIMENTAL TEST PLAN	3
TASK 2. SORBENT PREPARATION AND CHARACTERIZATION	3
Sorbent Preparation	3
Sorbent Characterization	4
TASK 3. BENCH-SCALE TESTING	8
Bench-Scale Test Results	8
Single Particle Kinetic Studies at LSU	9
TASK 4. BENCH-SCALE TEST ANALYSIS	10
REFERENCES	11
APPENDIX A	
X-RAY DIFFRACTION RESULTS	12

LIST OF TABLES

	<u>Page</u>
Table 1. Zinc Ferrite Pellet Characteristics	5
Table 2. Zinc Ferrite Extrude Characteristics	6
Table 3. Calculated Percent Sulfur Loading for 10 Cycles of Bench-Scale Testing Using Base Case Sorbent UCI T-2465	8

LIST OF FIGURES

Figure 1. Crush strength versus bulk density.	7
Figure 2. Loss on attrition versus bulk density.	7
Figure 3. Weight gain versus time at 550°C.	10

SUMMARY

AMAX Research & Development Center (AMAX R&D) has been investigating methods for improving the reactivity and durability of the zinc ferrite desulfurization sorbent. Zinc ferrite sorbents are intended for use in desulfurization of hot coal gas in integrated gasification combined cycle (IGCC) or molten carbonate fuel cell (MCFC) applications. The reactivity of the sorbent may be defined as its sulfur sorption capacity at the breakthrough point in a bench-scale fixed-bed reactor. The durability may be defined as the ability of the sorbent to maintain its reactivity and other important physical characteristics such as size, strength, and specific surface area during 10 cycles of sulfidation and regeneration. Two base case sorbents, spherical pellets and cylindrical extrudes used in related METC sponsored projects, are being used to provide a basis for the comparison of physical characteristics and chemical reactivity.

During the third quarter of the project (April - June, 1987), eight additional formulations of pellet and extrude sorbents were prepared and characterized following induration under different conditions. Cyclic testing of the base case cylindrical extrudes (United Catalyst T-2465) was completed. Eight test cycles using the base case spherical pellets (AMAX 1094-59) were also completed. Single particle kinetic studies were conducted at Louisiana State University using selected sorbent samples prepared at AMAX R&D.

In general, the extrude sorbents have resulted in greater crush strength, higher bulk density, and lower loss on attrition than the pellet sorbents. A relationship was observed between bulk density and the loss on attrition of indurated sorbents. A relationship between bulk density and crush strength of spherical pellets was also observed.

Good reactivity has been observed in selected samples representing both the cylindrical extrude and spherical pellet sorbent shapes. The reason for poor reactivity observed in some sorbents is being investigated. The single particle kinetic studies performed at LSU have shown differences in sulfidation response between the base case sorbents and the new sorbent formulations.

INTRODUCTION

The U. S. Department of Energy (DOE), through the Morgantown Energy Technology Center (METC), has been investigating a number of advanced systems for producing electric power from large coal reserves available in the United States. The integrated gasification combined cycle (IGCC) concept has been identified as one of the most promising technologies for coal utilization. The goal of hot coal gas cleanup programs at METC is to develop contaminant control technologies that operate under conditions compatible with those of the gasifier and power generator (gas turbine or molten carbonate fuel cell).

Sulfur control at high temperature and pressure forms a major portion of the hot gas cleanup program at METC. Previous research has established that high-temperature desulfurization can be accomplished using solid zinc ferrite sorbents to remove sulfur species from the coal gas to the 10 ppmv level or less, and the sorbent can be regenerated with air for reuse. The zinc ferrite sorbents experience chemical, physical, and thermal changes during sulfidation and regeneration. Deterioration of sorbent performance and physical characteristics is strongly influenced by the chemical composition of the sorbent and the method of preparation.

The objective of the present contract is to systematically investigate methods for enhancing the physical durability and chemical reactivity of the zinc ferrite desulfurization sorbent.

The program is divided into the following five tasks:

- Task 1. Experimental Test Plan
- Task 2. Sorbent Preparation and Characterization
- Task 3. Bench-Scale Testing
- Task 4. Bench-Scale Test Analysis
- Task 5. Topical Report

Accomplishments made during the 3rd quarter for each of the major tasks are summarized in the following sections.

ACCOMPLISHMENTS

TASK 1. EXPERIMENTAL TEST PLAN

No changes were made to the experimental test plan. The test plan was described in previous technical progress reports.^{1,2}

TASK 2. SORBENT PREPARATION AND CHARACTERIZATION

Sorbent Preparation

A total of five spherical pellet and five cylindrical extrude formulations from the statistical screening design test matrix have been successfully prepared. The screening test matrix calls for another seven pellet and seven extrude formulations to be prepared. Following induration at temperatures between 1,500 and 1,900°F for time periods between 15 minutes and 4 hours, a total of 27 pellet samples and 25 extrude samples have been prepared. Extrudes and pellets were prepared using both pigment-grade and catalyst-grade iron oxides. ZnO/Fe₂O₃ ratios of 0.8 and 1.0 (molar) have been used. Pellets containing up to 10 percent bentonite binder have been prepared. Extrudes containing up to 5 percent bentonite binder have been prepared. Pellets and extrudes containing organic binders were also included in the formulations which have been prepared so far.

The disk pelletizer was converted from 14 to 20 inches in diameter. This conversion allows for a higher pellet production rate and the use of a continuous fine water spray for more uniform pellet formation. No problems have been encountered in the preparation of spherical pellets within the range of feedstock compositions specified in the test matrix. The disk pelletizer is typically operated at an angle of 45° and at speeds of about 13 to 15 rpm. The solids feed rate is adjusted on the basis of the pellet growth rate, which is dependent on the content of binders and on the type of iron oxide used. In general, pellets formulated from the pigment-grade iron oxide have smooth surfaces, while those formulated from the catalyst-grade iron oxide have somewhat rough surfaces. Apparently, the coarser particle size of the catalyst-grade iron oxide results in more rapid and irregular pellet growth. The spherical pellets are sized by screening to reject oversized pellets and to recycle undersized pellets back to the pelletizer.

The rotary cutter installed on the extruder provides sorbents of uniform diameter (3/16 inch) with some variation in length due to the slightly different extrusion velocities through the six holes in the extrusion plate. Extrude lengths between about 1/4 and 3/4 inch are typically produced. The extrude formulations that include 10 percent bentonite have been difficult to prepare due to sticking and plugging inside the extrusion chamber. If possible, extrude sorbents containing a 10 percent bentonite formulation will be prepared by adjustment of the feed moisture content and possibly by modification of the extrusion auger.

Sorbent Characterization

The sorbent characterization methods were described in the second quarterly technical progress report.² These methods, which are based on ASTM standard test procedures or on standard procedures developed at AMAX R&D, are being used to evaluate sorbent properties. Tables 1 and 2 summarize the results of characterizations performed on the base case and other pellet and extrude formulations. The characterization results are discussed below.

Bulk density, crush strength, and the loss on attrition were measured for each of the sorbent formulations following induration under different conditions. Surface area analysis and single particle kinetic studies were conducted on selected samples. Based on the overall sorbent characteristics, conditions were selected for induration and subsequent cyclic testing of larger quantities of sorbent in the AMAX R&D fixed-bed reactors.

A correlation was observed between bulk density and crush strength for the spherical pellet sorbents. Crush strength determinations for extrude sorbents are less accurate than for pellets due to the variable contact surface area of different length extrudes on the plates of the compression crush strength test apparatus. The spherical pellet sorbents have a much more uniform area of contact (a single point) with the crush strength test plates. Figure 1 shows the crush strength as a function of bulk density for the spherical pellets and the cylindrical extrudes using the available test results. These results suggest that bulk density can be used as a guideline in projecting the strength of the pellets. No particular relationship was noted for the extrudes, although many of the extrude sorbents exhibited crush strengths greater than the maximum measurement capability (50 pounds) of the instrument being used.

A correlation between bulk density and the loss on attrition was noted for both the pellet and extrude sorbents. Figure 2 shows the relationship using the available test information. Note that the loss on attrition for extrudes falls into a much narrower range than for the pellets. All extrudes prepared so far exhibit bulk densities greater than 1.1 g/ml, while most of the pellet formulations result in bulk densities less than 1.1 g/ml. The loss on attrition increased rapidly as the bulk density of the pellets dropped below 1.00 g/ml.

The sorbents which were indurated at 1,500°F generally exhibited the lowest crush strengths and the highest loss on attrition. Some X-ray diffraction analyses of sorbents indurated at 1,500°F (E2 and E7) showed that the ferrite phase was completely formed in that no zinc oxide peaks were present. (Some iron oxide was shown to be present in the sorbent containing a 0.8 ZnO/Fe₂O₃ ratio.) The same sorbent formulations which were indurated at 1,900°F (E4 and E9) exhibited X-ray patterns similar to the samples indurated at lower temperature. Appendix A summarizes the X-ray diffraction results. Although zinc ferrite was observed in the samples indurated at different temperatures, the sorbents which were indurated at higher temperatures exhibited lower surface area, indicating some grain growth and consolidation.

Table 1. Zinc Ferrite Pellet Characteristics

Sorbent Sample Number	Pellet Formulation				Induration		Physical Properties				BET	
	Run	Fe ₂ O ₃	ZnO/ Fe ₂ O ₃	% Bentonite	Starch	Temperature, °F	Time, Hours	Bulk Density, kg/l	Crush Strength, lb	Loss on Attrition, Percent	Surface Area, m ² /g	Samples Sent to LSU
	No.	Grade		%					x	s		
P1	2	P	0.8	2	0	1,500	0.25	0.876	4.6	1.8	65.1	
P2						1,500	4.00	0.912	3.8	1.5	76.7	
P3						1,700	2.00	0.916	4.8	1.5	60.2	
P4						1,700	2.00	0.860	5.7	2.8	54.0	
P5						1,900	0.25	0.952	6.6	3.7	51.5	x
P6						1,900	4.00	1.529	40.3	10.7	1.28	x
P7	3	C	1.0	2	0	1,500	0.25	0.999	9.3	4.4	42.8	
P8						1,500	4.00	0.952	6.8	2.9	40.7	
P9						1,700	2.00	1.013	10.0	4.8	33.7	
P10						1,700	2.00	1.048	10.1	4.1	31.6	x
P11						1,900	0.25	1.036	10.5	4.1	32.4	x
P11A						1,900	0.25	1.141	16.6	6.0	2.63	
P12						1,900	4.00	1.273	21.5	10.2	1.38	
P13	5	C	0.8	2	2	1,500	0.25	1.028	14.5	3.3	16.2	
P14						1,500	4.00	1.034	17.6	5.5	18.7	
P15						1,700	2.00	1.075	18.2	5.5	13.8	
P16						1,900	0.25	1.196	27.3	5.4	10.7	1.55
P17						1,900	4.00	1.339	32.8	5.3	1.43	
P18	19	C	1.0	10	0	1,500	0.25	0.956	10.2	1.8	36.5	
P19						1,500	4.00	0.955	11.3	2.5	33.5	
P20						1,700	2.00	0.952	11.6	2.6	32.0	
P21						1,900	0.25	0.955	12.3	3.4	29.7	x
P22						1,900	4.00	1.132	20.8	6.6	22.8	
P23	21	C	0.8	10	2	1,500	0.25	0.914	5.7	2.3	42.4	
P24						1,500	4.00	0.902	7.1	2.5	39.0	
P25						1,700	2.00	0.922	10.4	1.9	35.0	
P26						1,900	0.25	0.956	15.0	3.5	25.5	
P27						1,900	4.00	1.111	21.2	4.8	19.9	

P = Pigment grade.

C = Catalyst grade.

x = Average single pellet crush strength.

s = Standard deviation (25 measurements).

tbd = To be determined.

1094-59 base case pellets: x = 5.1, s = 2.9, bulk density = 1.014 kg/l, loss on attrition = tbd, surface area = 1.01 m²/g. An "A" designation following the sorbent sample number indicates a sample used for cyclic sulfidation testing.

Table 2. Zinc Ferrite Extrude Characteristics

Sorbent Sample Number	Extrude Formulation					Induration Conditions		Physical Properties				BET	
	Run No.	Fe ₂ O ₃ Grade	ZnO/ Fe ₂ O ₃	Bentonite %	Methocel %	Temperature, °F	Time, Hours	Bulk Density, kg/l	Crush Strength, lb x	Loss on Attrition, lb Percent	Surface Area, m ² /g	Samples Sent to LSU	
E1	1	C	0.8	2	0	1,500	0.25	1.199	29.4	7.0	9.8		
E2						1,500	4.00	1.120	42.5	8.5	7.7	4.39	
E3						1,700	2.00	1.159	39.1	8.0	11.9		
E4						1,900	0.25	1.172	46.2	8.0	8.2	3.59	
E5						1,900	4.00	1.355	>50		5.7		
E6	4	P	1.0	2	0	1,500	0.25	1.130	24.6	4.6	16.5		
E7						1,500	4.00	1.154	26.0	6.1	18.2	x	
E8						1,700	2.00	1.147	24.2	6.3	14.1		
E9						1,900	0.25	1.354	46.8	11.7	6.6	2.74	
E10						1,900	4.00	1.501	>50		4.9		
E11	7	C	1.0	2	0.5	1,500	0.25	1.215	31.8	8.5	12.2	x	
E12						1,500	4.00	1.196	33.3	6.5	13.3		
E13						1,700	2.00	1.148	37.7	6.6	15.5	x	
E14						1,900	0.25	1.272	>50		8.3		
E15						1,900	4.00	1.623	>50		6.8		
E16	9	C	0.8	5	0	1,500	0.25	1.269	>50		6.1		
E17						1,500	4.00	1.238	>50		9.4		
E18						1,700	2.00	1.231	>50		10.8		
E19						1,900	0.25	1.367	>50		8.5	2.51	
E20						1,900	4.00	1.743	>50		5.7		
E21	15	C	1.0	5	0.5	1,500	0.25	1.195	50		9.9		
E22						1,500	4.00	1.207	36.8	7.6	11.7		
E23						1,700	2.00	1.220	>50		10.2		
E24						1,900	0.25	1.300	>50		7.4	2.93	
E25						1,900	4.00	1.676	>50		5.3		

P = Pigment grade.

C = Catalyst grade.

x = Average single pellet crush strength.

s = Standard deviation (25 measurements).

T-2465 base case extrudes: x = 30.2 lb (after sulfidation 26.6), s = 6.3 (after sulfidation 16.3), bulk density = 1.306 kg/l, loss on attrition = 11.15%, surface area = 3.30 m²/g (fresh extrude), 1.53 m²/g (sulfidized extrude).

Figure 1. Crush strength versus bulk density.

Figure 2. Loss on attrition versus bulk density.

TASK 3. BENCH SCALE TESTING

Bench-Scale Test Results

Cyclic sulfidation and regeneration testing of the base case UCI T-2465 extrude sorbent was completed. Cyclic testing ended with the 10th cycle, during which sulfidation was carried out until the bed was saturated with sulfur and the exit gas composition contained the same hydrogen sulfide concentration as the entrance gas. This base case sorbent was tested in both of the bench-scale reactors for the full 10 cycles. Reactivity was maintained during the cyclic tests. Unlike some previous cyclic test results, the UCI T-2465 sorbent sulfur sorption capacity improved following the first cycle of sulfidation and oxidation. Table 3 summarizes the results. Some consistent difference in reactivity was noted between the two reactors. Reactor L exhibited sulfur loadings ranging from 13.7 to 28.6 percent at H₂S breakthrough. (Sulfur loadings are determined by dividing the calculated weight of sulfur captured, based on H₂S flow rate and time, by the starting sorbent weight in the reactor bed, times 100 percent.) Reactor R exhibited sulfur loadings ranging from 8.8 to 21.6 percent at H₂S breakthrough. The reason for these differences is not known; however, some differences in sorbent packing in the fixed-bed reactor columns could contribute to the differences in sulfur loading, particularly for the relatively short (18 inches) column height. Additionally, some differences in the temperature profile across the radius of the fixed bed could result from the difference in the three-zone furnace diameters. Reactor L is a 3-inch diameter furnace, while Reactor R is a 2.5-inch diameter furnace. Each reactor holds a 2.5-inch OD reactor pipe. In general, Reactor R is capable of somewhat more precise temperature control through the length of the reactor. As will be discussed, temperature can have a significant effect on the kinetics of sulfidation. It should be noted that upon sulfidation to saturation, the sorbents in both reactors exhibited the same level of sulfur content.

Table 3. Calculated Percent Sulfur Loading at Breakthrough for 10 Cycles of Bench-Scale Testing Using Base Case Sorbent UCI T-2465

<u>Reactor</u>	<u>Cycle 1</u>	<u>Cycle 2</u>	<u>Cycle 3</u>	<u>Cycle 4</u>	<u>Cycle 5</u>	<u>Cycle 6</u>	<u>Cycle 7</u>	<u>Cycle 8</u>	<u>Cycle 9</u>	<u>Cycle 10</u>	<u>At Saturation</u>
L	13.7	28.6	26.3	24.0	22.2	22.6	22.2	20.2	20.4	22.3	35.8
R	8.8	16.3	13.2	19.3	21.6	14.3	15.6	14.7	13.4	14.2	35.9

Following the completion of the cyclic testing of the UCI T-2465 base case extrude sorbent, the AMAX 1094-59 base case pellet sorbent was loaded into both reactors. Cyclic testing was suspended in Reactor R after three cycles in order to begin testing of one of the screening test design matrix sorbents. Eight cycles of testing were completed on the 1094-59 sorbent by the end of the reporting quarter. Poor reactivity was noted during each cycle. Some tests were conducted to determine

the cause of the poor performance. In one test, the sulfidizing gas flow rate in Reactor L was reduced to 2,000 bed volumes per hour from the 2,527 bed volumes per hour being used for most of the tests. The result was that a sulfur loading of 3.4 percent was achieved versus the 1.3 to 1.5 percent loading observed at the higher gas flow. The 2,527 bed volumes per hour provide the same mass flow of gas at the Golden, Colorado, AMAX R&D laboratory as 2,000 bed volumes per hour provide at the sea level test specification. Previous work at AMAX R&D used the same volumetric gas flow rate as called for at sea level, resulting in a lower mass flow of gas into the reactors. In a different test in Reactor R, the test temperature was increased to 650°C from the specified 550°C using the higher 2,527 bed volumes per hour gas flow rate. Sulfur loading under these conditions increased to 13.9 percent. This is comparable to sulfur loadings observed with similar sorbents in past AMAX work.³ Cyclic testing of the AMAX base case pellet was suspended in Reactor R following this test. The two tests demonstrate the sensitivity of the short, fixed-bed reactor to the gas flow rate and to the reaction kinetics, since only the lower portion of the bed functions to remove hydrogen sulfide prior to a breakthrough of H₂S at the 200 ppm level. In addition, the tests demonstrated the sensitivity of the AMAX base case sorbent to temperature. Far superior performance was noted at the higher test temperature. These differences in performance were not detected by the single particle kinetic studies, as will be discussed in the following section.

A new sorbent prepared at AMAX R&D, sample P11A, was loaded into Reactor R following testing with the base case pellets. The formulation of sample P11A is shown in Table 1. Good reactivity has been observed using this sorbent during the four cycles of testing which were completed at the end of the quarter. Sample P11A was made in a spherical pellet shape using catalyst-grade iron oxide. Up to 34.2 percent calculated sulfur loading at breakthrough has been achieved. The third sulfidation cycle was suspended prior to H₂S breakthrough as a result of plugging in the gas tubing leading to the reactor. Apparently some iron contamination in the carbon monoxide gas cylinder reacted with the hydrogen sulfide gas to form an iron/sulfur deposit just downstream of the point where hydrogen sulfide is introduced into the preheated reducing gas. The gas supplier has taken steps to avoid such contamination in the future.

Single Particle Kinetic Studies at LSU

Ten samples have been submitted for single particle kinetic studies at Louisiana State University. Included were the two base case sorbents. All of the single particle tests are currently being performed using a 2.7 percent hydrogen sulfide gas concentration, as reported in the previous quarterly technical progress report.² Figure 3 shows weight gain as a function of sulfidation time for UCI T-2465 and AMAX 1094-59 base case sorbents at a temperature of 550°C. The single particle kinetic studies indicate a faster reaction rate for the AMAX sorbent. These results conflict with the cyclic bench-scale fixed-bed reactor data discussed earlier. The reason for the difference in response is not known at this time. Some further work will be performed to determine the cause for the differences.

Figure 3. Weight gain versus time at 550°C.

TASK 4. BENCH-SCALE TEST ANALYSIS

Analyses of the UCI T-2465 base case sorbent were performed following sulfidation to saturation. Samples taken from the top, middle, and bottom sections of both reactors were analyzed for sulfur, iron, and zinc. The results indicated that zinc and iron values were very consistent at about 23.5 and 40.5 percent, respectively. Sulfur values varied between 29.3 and 31.1 percent without showing any definite trend based on the location of the sorbent in the reactors. X-ray diffraction analysis of the sorbent showed ZnS as a major constituent. Fe_xS_y minerals were also observed as major constituents. Some franklinite (perhaps 10 percent) was also noted. No ZnO or zinc silicates were observed. Electron microprobe analyses were pending at the end of the reporting period. Table 2 shows that the surface area of the sulfidized base case extrudes was $1.5 \text{ m}^2/\text{g}$ compared to $3.3 \text{ m}^2/\text{g}$ for the unreacted sorbent. Determinations of other physical properties such as crush strength, sorbent diameter, and loss on attrition are pending.

REFERENCES

1. Jha, M. C. and Baltich, L. K., "Enhanced Durability and Reactivity for Zinc Ferrite Desulfurization Sorbent", Quarterly Technical Progress Report 1, October - December, 1986, AMAX Research & Development Center, DOE Contract No. DE-AC21-86MC23172, February 23, 1987.
2. Jha, M. C., Baltich, L. K., and Berggren, M. H., "Enhanced Durability and Reactivity for Zinc Ferrite Desulfurization Sorbent", Quarterly Technical Progress Report 2, January - March, 1987, AMAX Research & Development Center, DOE Contract No. DE-AC21-86MC23172, May 18, 1987.
3. Jha, M. C., Hepworth, M. T., and Baltich, L. K., "Enhanced Sorbent Durability for Hot Coal Gas Desulfurization", Final Report, AMAX Extractive Research & Development Center, DOE Contract DE-AC21-84MC21168, March 1986.

APPENDIX A
X-RAY DIFFRACTION RESULTS

AMAX RESEARCH & DEVELOPMENT CENTER
INTEROFFICE MEMORANDUM

Subject: Phase Constituents in Zinc Ferrite
Extrudes (80270)

July 27, 1987

To: M. Berggren

From: J.R. Odekirk

Samples of roasted (indurated) zinc ferrite extrudes and iron oxide feedstock were analyzed by X-ray diffraction to determine the phases present. Phases detected are as follows:

Iron oxide feedstocks

Phases

Pigment - Grade
Catalyst - Grade

Hematite
Hematite

Zinc ferrite extrudes

Phases

E-2 (1500°F, 4 hrs)
E-4 (1900°F, 15 mins)

Franklinite (90%), Hematite (10%)
Franklinite (95%), Hematite (5%)

E-7 (1500°F, 4 hrs)
E-9 (1900°F, 15 mins)

Franklinite (100%)
Franklinite (100%)

The four zinc ferrite extrudes contained franklinite ($\text{Zn Fe}_2\text{O}_4$) except that samples E-2 and E-4 also contained unreacted hematite. Sample E-4 which was indurated at a higher temperature appears to contain less hematite.

J.R. Odekirk

/lc

cc: A. Blandon
R.M. Rowe

MIN No. 87-8

END

**DATE
FILMED
9/01/92**